0006490

1 OF 1

Report DOE/PC/89771-12
Grant DE-FG22-89PC89771

TWELFTH QUARTER REPORT
July 1 - August 31, 1992

Received by OSTI

J'

MECHANISM OF HYDRODENITROGENATION (Part 12) DOE/PC/89771--12
PREPARATION OF SUPPORTED Ru CATALYSTS DE93 006490

Raul Miranda
Department of Chemical Engineering
University of Louisville
Louisville, KY 40292, USA

contents

Abstract	2
Introduction	2
Experimental	4
Discussion	4
Acknowledgements	6
References	7

ep

MASTER

ABSTRACT

A series of Ru oxide catalysts has been prepared and partially characterized. Starting from $\text{Ru}(\text{NO})(\text{NO}_3)_3$ to avoid residual Cl in the catalysts, Ru^{+3} oxides have been prepared in loadings of 1, 4 and 8 wt%, over silica, gamma-alumina and silica-aluminas of controlled acidity. The highly dispersed oxides are produced in order to study the controllability of the various types of catalytic functionalities present on HDN catalysts.

INTRODUCTION

Efficient nitrogen removal from heterocyclic aromatics in liquid fuels calls for the development of catalysts with better HDN activity than is available with the traditional HDS catalysts, such as $\text{CoMo}/\gamma\text{-Al}_2\text{O}_3$ and $\text{NiMo}/\gamma\text{-Al}_2\text{O}_3$. Over these catalysts, the first step is the partial or total hydrogenation of the heterocyclic ring -- at equilibrium at normal operating conditions -- and the rate-limiting step is the scission of the C-N-C bonds. Therefore an increase in the rate of C-N-C scission should produce an overall increase in the HDN yield.

In this project it is proposed that the selectivity of the HDN reaction can be affected by an alteration of the catalyst acidity since it is possible that an acidic Hofmann-like deamination pathway is operative [1] in parallel with the hydrogenolysis of saturated C--N--C bonds. Such was the conclusion from the study done of the denitrogenation of piperidine [3], where it was demonstrated that Bronsted acid sites are active for the denitrogenation of N-heterocycles, whereas Lewis sites are not.

To understand better the role of acidic sites in the presence of hydrogenation and hydrogenolysis sites, molybdena was supported on a series of acidic aluminas, and the resulting new acidity and molybdenic phases were characterized [4]. The new acidity, of both Lewis and Bronsted type, was accompanied by changes in the state of oxidation of Mo [5,6]. The silica-rich supports favor more reducible phases, including a segregated $\text{Al}_2(\text{MoO}_4)_3$ phase, which presumably will have different hydrogenation and hydrogenolysis sites than the less reducible phases, which are favored by alumina-rich supports. It must be noticed that pure gamma-alumina

does not lead to the formation of $\text{Al}_2(\text{MoO}_4)_3$. This is only formed upon calcination of Mo oxides over silica-rich silica-aluminas, and is highly reducible [6]. Pure silica supports favor the agglomeration of a definite phase of MoO_3 , which is also highly reducible. In these complex catalysts, a varying number of hydrogenolysis sites will be accompanied by a varying number of acidic sites, and their combined roles will affect the activity and selectivity for HDN.

The HDN reaction of pyridine was utilized to assess the variation in activity and selectivity produced by the nature of the support [7]. The results revealed that for silica-alumina supports (>50 wt% silica) the optimum loading of molybdena is 4 wt%. At this low loading the activity and selectivity towards HDN were maximum. The main parameters affecting the activity and selectivity are here postulated to be Mo reduction state and surface acidity. Thus low-temperature oxygen chemisorption was utilized to investigate surface reducibility of near-surface Mo, and effect of catalyst loading and support composition on such reducibility [8].

A mechanism was then postulated for an acid-catalyzed denitrogenation involving the Bronsted acid sites present on the support and molybdena-support interface, since strong Bronsted sites on the molybdena phase itself were shown not to be formed. The participation of Bronsted acid sites was verified by exchange of surface hydroxyl hydrogen with deuterium [9-11]. Finally, the Hofmann elimination of piperidine beta-hydrogen was verified by infrared spectroscopy and mass spectrometry [12].

In spite of the significance of an acidic pathway leading to pyridine and piperidine denitrogenation, it is important to emphasize that hydrogenation of the aromatic molecules must be performed to some extent before acid sites are able to quaternize the nitrogen hetero-atom and to remove the piperidine beta-hydrogen. It is thus important to notice that the high hydrogenation activity that is needed necessarily leads to high hydrogenolysis activity in the case of Mo catalysts, and hence to high production of smaller alkanes.

In view of this difficulty in controlling the reaction selectivity, it becomes apparent that to balance the population of various sites (hydrogenation, hydrogenolysis and acidic sites), an additional or alternate catalyst component is needed. Such component may provide, for example, high hydrogenation but low hydrogenolysis activity, thus leading to high acidic selectivity.

Reports of the high activity of Ru sulfide catalyst for HDN make Ru a good candidate for incorporation into acidic Mo catalysts. In principle, the high hydrogenation activity of reduced Ru oxide can be conveniently exploited without

extensive reduction of the Mo oxide. The reducibility of Ru oxides is known to be higher than that of Mo oxides, thus milder reduction conditions could be used to obtain less reduction of Mo and thus less hydrogenolysis activity.

Various questions must be answered to assess the role of Ru addition in the overall mechanism of HDN, such as effect of Ru on acidity, and effect of the support composition on Ru oxide structure. Therefore during this period of the project, a series of silica-alumina supports has been prepared and characterized by BET, and Ru oxide has been supported in different loadings over these supports.

EXPERIMENTAL

Synthesis of Supports and Supported Ruthenium Oxide

Fresh batches of silica-aluminas were prepared with compositions of 25, 50 and 75 wt% silica. Separately, pure silica and gamma-alumina were also synthesized from the same precursors as the silica-aluminas. The supports were characterized by BET surface area, and will be characterized in subsequent work by ammonia chemisorption and TPD, and IR of adsorbed pyridine. Details of the support preparation have been given before [2].

Supported Ru oxide was prepared by incipient impregnation method from $\text{Ru}(\text{NO})(\text{NO}_3)_3$, as described in reference 13. The support pore volume was measured by water absorption. Appropriate amount of Ru salt was dissolved in acidified distilled water to produce catalysts with loadings of 1, 4 and 8 wt% of Ru_2O_3 . After impregnation, the solids were dried for 24 h at room temperature and 4 h in air at 383K. The catalysts were then loaded in the BET adsorption cell and heated to 573K under vacuum to decompose the nitrates and remove N oxides. BET surface area was then measured following standard techniques [1]. A total of 15 different sample compositions were produced with BET surface areas between 250 and 300 m^2/g , in agreement with our previous work on supported Mo [1].

DISCUSSION

The control of the different types of functionalities present on supported oxides allows in principle the design of catalysts with optimized selectivity. In the case of HDN catalysis we have learned that it is relevant to control the number and density

of hydrogenation, hydrogenolysis and acidic scission sites. While in our recent work with Mo we were able to vary the amount and type of acid sites and the amount of reduced Mo sites, we were not able to control the hydrogenation activity without altering the hydrogenolysis activity. Both functions depend upon the state of oxidation of the Mo, which is mostly a function of support composition and Mo oxide loading. The introduction of a second, more reducible transition metal, Ru, provides us with another degree of freedom to alter the ratio of hydrogenation to hydrogenolysis activity.

It is pertinent to observe that the use of Ru sulfide in HDN has been practically demonstrated [14] after various authors showed that the volcano plot for HDS catalysis has a maximum on Ru sulfide. It is also pertinent to observe that the optimum HDN catalyst in that work consisted of Ru sulfide supported on Y-zeolite, a strongly Bronsted acidic support, although high temperature was required for good selectivity. At lower temperature (about 300°C) the high hydrogenation and low hydrogenolysis activities which are characteristic of Ru, were observed. Therefore, the strategy proposed in this work, that is, to control hydrogenation activity by means of Ru sites, hydrogenolysis activity by means of Mo sites, and acidic scission activity by means of Bronsted/Lewis sites, has some empirical support. Likely important is to consider the lifetime of Ru catalysts. It is well known that deactivation of Ru sulfide in HDS reactions has prevented its use. However, at least in the case of HDN it has been demonstrated that addition of Ru to Mo catalysts results in Ru species that are resistant to deactivation [15].

Following the style of our previous work, we have initially prepared supports with variable amount and type of acidity, from pure Lewis acidic gamma-alumina, to increasingly Bronsted acidic silica-aluminas. On these supports, we have deposited Ru oxide to various loading levels, altering the overall acidity of the catalysts. There is no systematic work on the effect of Ru oxide coverage on the acidity of supports, thus that question will be answered by this research. There are works, however, on the role of Ru precursors on the resulting properties of catalysts. In particular, highly interacting Ru with supports produced better HDN catalysts than less interacting ones [14]. High interaction with zeolitic supports was obtained by ion exchange with $[\text{Ru}(\text{NH}_3)_6]^{3+}$, as opposed to impregnation with Ru chloride or deposition from Ru carbonyls. Such result is not as relevant for our work since we are not attempting to produce Ru metal but Ru oxides in strong interaction with the supports. Of more importance is the result obtained by various authors that Cl is hard to remove by reduction and interferes with hydrogen chemisorption [16]. Additionally, in our work, Cl would interfere with the control of the acidic functionalities. Thus, to completely avoid the presence of Cl in the preparation, and to produce supported Ru oxide, the precursor salt chosen here is $\text{Ru}(\text{NO})(\text{NO}_3)_3$.

The degree of dispersion of the oxide, and thus its degree of interaction with the support and its reducibility, is affected by the extent of precursor reaction with the support OH, and by the conditions of drying, calcination and reduction. The reaction with the support is hereby controlled by the pH of the impregnating solution. Acidic pH have been observed to produce more uniform, sheet-like, distribution of oxide than neutral or basic pH [17]. Drying is performed under mild conditions (room temperature, followed by heating to 373 K) and calcination is performed at 573K in the absence of oxygen, since oxygen leads to oxidation and sintering of Ru⁺. The final treatment, reduction, is performed in situ prior to reaction, at 573K with 10% hydrogen-helium mixture. The acidity, reduced Ru oxide dispersion, and catalytic activity for pyridine HDN will be tested in subsequent work.

ACKNOWLEDGEMENTS

Funding

This work was carried out with funds from DOE (Grant DE-FG22-89PC89771), partial support from NSF (Grant No. RII-8610671) and from the Commonwealth of Kentucky (EPSCoR Program).

Personnel

Jorge Marzari, PhD student

REFERENCES

1. N. Nelson and R. B. Levy, J. Catal. 58(1979)485
2. R. Miranda, "Mechanism of Hydrodenitrogenation. Part I: Preparation and Characterization of Acidic Supports", DOE Report DOE/PC/89771-1, January 1990.
3. R. Miranda, "Mechanism of Hydrodenitrogenation. Part II: Piperidine Denitrogenation over Silica-Aluminas", DOE Report DOE/PC/89771-2, April 1990.
4. R. Miranda, "Mechanism of Hydrodenitrogenation. Part III: Preparation and Characterization of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-3, July 1990.
5. R. Miranda, "Mechanism of Hydrodenitrogenation. Part IV: Infrared Spectroscopy of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-4, October 1990.
6. R. Miranda, "Mechanism of Hydrodenitrogenation. Part V: X-Ray Diffraction of Supported Molybdena Catalysts", DOE Report DOE/PC/89771-5, January 1991.
7. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VI: HDN of Pyridine over Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-6, April 1991.
8. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VII: Low Temperature Oxygen Chemisorption of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-7, June 1991.
9. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VIII: H₂-D₂ Exchange in Non-Acidic and Acidic Supports", DOE Report DOE/PC/89771-8, September 1991.
10. R. Miranda, "Mechanism of Hydrodenitrogenation. Part IX: H₂-D₂ Exchange in Reduced Mo Catalysts", DOE Report DOE/PC/89771-9, December 1991.

11. R. Miranda, "Mechanism of Hydrodenitrogenation. Part X: Adsorption of Piperidine on Reduced Mo Catalysts", DOE Report DOE/PC/89771-10, March 1992.
12. R. Miranda, "Mechanism of Hydrodenitrogenation. Part XI: Beta-Hydrogen Elimination", DOE Report DOE/PC/89771-11, June 1992.
13. X. Wu, B.C. Gerstein, T.S. King, J. Catal. 118, 238-254 (1989)
14. T.G. Harvey, T.W. Matheson, J. Catal. 101, 253-261 (1986)
15. A.S. Hirschon, R.B. Wilson, R.M. Laine, Appl. Catal. 34, 311-316 (1987)
16. T. Narita, H. Miura, K. Sugiyama, T. Matsuda, R.D. Gonzalez, J. Catal. 103, 492-495 (1987); K. Lu, B.J. Tatarchuk, J. Catal. 106, 166-175 (1987); *ibid.*, 106, 176-187 (1987)
17. A. Bossi, F. Garbassi, A. Orlandi, G. Petrini, L. Zanderighi

END

DATE
FILMED
319193