The Prospects for Polarized Target Materials with Pure Carbon Background*

D. A. Hill

High Energy Physics Division
Argonne National Lab, Argonne, IL 60439

October 6, 1992

ANL-HEP-TR--92-88

DE93 002987

1 Introduction

None of the materials presently in common use for polarized proton targets has a pure carbon nuclear background. The alcohols and diols contain some oxygen, and the ammonia and amine-based materials contain nitrogen and/or other non-carbon species. In the latter cases the noncarbon nuclei are measurably polarized as a concomitant of the process used to polarize the hydrogen nuclei. The relative simplicity of a pure carbon background (unpolarized, aside from the ^{13}C present at $\approx 1\%$ natural abundance) would be advantageous for most types of scattering experiments and perhaps crucial for some. In addition to simplifying the kinematics of background events, pure carbon is relatively easy to prepare as a "dummy" target for background subtraction. Also, in such a target material, ^{13}C -enrichment would yield a clean polarized ^{13}C material (with only a polarized H background).

In this note I explore the possibilities for such materials, touching upon only what I consider to be the "high" points. The subject matter is capable of nearly endless ramification and speculation. In fact, owing to a general lack of relevant experimental data, even this relatively brief note contains much that is speculative to some degree.

To date, all practical polarized solid targets have relied on some method of paramagnetic doping in order to achieve large nuclear spin polarization. The paramagnets are embedded in the solid matrix and, at modestly low temperatures and moderately high magnetic fields, attain a high spin polarization that can be transferred to the surrounding matrix nuclei by the application of microwave spin-pumping, a process that is one form of dynamic nuclear polarization (DNP). This fairly simple recipe works very well in a wide variety of matrices and with a wide variety of doping methods, if one is satisfied with modest enhancements of the nuclear polarization. However, if one is after polarizations that are a sizable fraction of 100%, the recipe almost never works. Optimal results depend on the compliance of a number of parameters. Some of the parameters are not very easy to quantify in practice,

* Work supported by the U. S. Department of Energy, Division of High Energy Physics, Contract No. W-31-109-ENG-38.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

and so we are left with an irreducible component of trial-and-error. (Even when dealing with a well-known and much-used polarized target material, we may not understand in great detail "why it works.") One degree of freedom is the choice of doping method, and I have subdivided this note along that line.

In what follows, the term "hydrocarbon" is used in its strict sense of "material containing only carbon and hydrogen." The term "proton" is short for "nucleus of a hydrogen atom" (as opposed to protons bound in complex nuclei), unless otherwise noted. Also, the common names isobutane, isopentane, and neopentane are used for 2-methylpropane, 2-methylbutane, and 2,2-dimethylpropane, respectively.

2 Radiolytic doping

Two general methods of doping have had some success, "radiolytic" and "chemical." I will consider the latter method in a separate section. In general, the "radiolytic" method may be divided into the following categories according to the physical approach:

- *Radiation damage.* The solid matrix material is irradiated with a particle beam, fission reactor flux, or a radioactive source. A fraction of the starting material is converted *in situ* to paramagnetic fragments. The irradiation must usually be carried out at cryogenic temperatures in order to stabilize the paramagnets in sufficient type and number.
- *Photolysis.* In this case the energy required to break molecular bonds is supplied by light. Photolysis may be carried out *in situ* in the liquid phase or directly in the (usually cold) solid, but more typically the photolytic products are created in gas phase and then frozen onto a cold substrate. The photolysis may act directly on the primary matrix material or on a secondary stream of some other substance which is then mixed into it prior to condensation.
- *RF discharge.* This method differs from photolysis only in that the energy is supplied by a radiofrequency field. I suppose that high-voltage low-frequency discharge could also be used, but one sees little mention of it in the literature.

In each of these procedures, the resulting type and density of paramagnet often depends not only on the chemical nature of the matrix, on the type, dose rate, and total dose of radiation, and on the temperature of the process, but also on the physical state of the matrix (e.g., amorphous or crystalline) and on any subsequent thermal experience of the solid (e.g., annealing). The paramagnets produced may be charged (e.g., molecular ions, trapped electrons) or neutral free radicals (atoms or molecules containing unpaired electrons).

There are currently two polarized target materials, ammonia and ^6LiD , that are successfully produced by using radiolysis. In both cases, the approach used is radiation damage with particle beams. For ^6LiD this is probably the only practical approach. For ammonia, the photolytic and discharge approaches might also work, although they have never been tried, to my knowledge. The paramagnets produced in ammonia are primarily $\cdot\text{NH}_2$ radicals; those in ^6LiD are F-centers (a type of trapped electron).

2.1 Past attempts to dope hydrocarbons radiolytically for DNP

There has been very little work reported on DNP with radiolytically-doped hydrocarbons. I summarize here what little is known, listing the materials in order of increasing relative hydrogen content.

Fluorene

The protons in fluorene ($\text{C}_{13}\text{H}_{10}$) have been polarized to 42% at 1.4 K, 2.7 T [1]. The doping approach was basically photolytic: Crystals of fluorene containing a small admixture of perdeuterated phenanthrene were loaded into a DNP refrigerator, which was standard except that optical access to the sample was provided. DNP was accomplished by using simultaneous application of microwaves and uv light. The uv light excites metastable molecular triplet states of the phenanthrene impurity, and the microwaves couple these to the surrounding nuclei. This process is called "Microwave Induced Optical Nuclear Polarization" (MIONP). The authors felt that polarization >80% might be achieved at higher fields or lower temperatures. The most notable feature of this work is the fact that the paramagnets (triplet states) can be "turned off" after polarizing, simply by turning off the uv, leading to a long lifetime of the nuclear polarization at modest fields and temperatures.

Polyethylene

Polyethylene (CH_2) has been neutron-irradiated at room temperature, with subsequent DNP carried out at 1.2 K, 2.5 T [2]. The maximum proton polarization achieved was 10%. The authors felt that this result might be improved upon by using irradiation at low temperature, but such tests were never made.

Ethane

A proton DNP of 10% has been reported [3] for beam-irradiated ethane (C_2H_6) at 1 K, 5 T. Presumably the paramagnets were ethyl radicals ($\cdot\text{C}_2\text{H}_5$). Apparently the authors were pessimistic about improving this result. Since few of the experimental details were reported, it's difficult to judge if their pessimism is fully justified. In this case, it may be important to note that we know of some materials that polarize very well at 2.5 T but very poorly at 5 T [4].

Methane

Radiolytic methyl radicals ($\cdot\text{CH}_3$) have been produced in solid methane (CH_4) by a great number of workers [5, pp. 131–133], however, the outlook for successful DNP is poor. As late as 1979, Glättli [6] was still entertaining some hopes, but his subsequent publications do not mention DNP. Owing to rapid reorientational quantum tunneling by one of the low-lying nuclear spin isomers, the proton spin-lattice relaxation rate is apparently too large to support useful levels of DNP [7].

2.2 Possible candidates for future work

One could blindly select almost any hydrocarbon, irradiate it, and look for DNP. Experience tells us that this sort of “shotgun” approach has a low rate of return on time and money invested. Hence, we should look for selection principles that will allow us to limit our choices to those possibilities that seem more likely of success. In general, radiation chemistry tends to be very messy. This is one of the disadvantages of the radiolytic doping method. In particular, in many substances a number of different paramagnetic species are produced under the same irradiation conditions. For reasons that I will not go into here, microwave DNP tends to be rather unsuccessful when there are competing species of paramagnet present. It seems to me that one useful selection principle, therefore, is to consider substances that yield just one primary paramagnetic species upon irradiation. Examination of the literature at hand, primarily Ref. [5], suggests that the following hydrocarbons (other than methane and ethane) may have this property:

Hydrocarbon	Primary radical	Hydrocarbon	Primary radical
propane (C_3H_8)	isopropyl	cyclopentane (C_5H_{10})	cyclopentyl
n-butane (C_4H_{10})	isobutyl	cyclohexane (C_6H_{12})	cyclohexyl
n-pentane (C_5H_{12})	isopentyl	ethene (C_2H_4)	ethyl
neopentane (C_5H_{12})	neopentyl	propene (C_3H_6)	allyl

As one goes to larger molecules than these, the radiation chemistry becomes more complex. Even for the above cases, some modest thermal cycling might be needed after radiolysis to anneal out unwanted species such as trapped electrons and H-atoms.

There are some practical considerations that we could use to further narrow the selection. The melting points of propane (≈ 85 K) and propene (88 K) are below the temperature (≈ 90 K) of the liquid argon (LAr) cryostats that are normally used for material irradiation. If we want to use existing cryostats, we may not want to consider propane and propene. Also, ethene (m.p. 104 K) is marginal in this respect. Furthermore, there is the question of solubility of the hydrocarbon in LAr (a question that is not unrelated to the melting point). Propane is evidently highly

soluble in LAr [8]. Even in LN₂ (77 K), the solubility of propane is not entirely negligible ($\approx 10^{-3}$ mole fraction) [8]. We may guess that ethene and propene have a similar problem. Even butane may be marginal in this respect. It has a solubility of $<10^{-4}$ in LN₂, which is probably small enough for our purposes, but the solubility in LAr may be as high as 10^{-3} [8]. We may consider bypassing solubility problems (at least during the irradiation process) by using indirect cooling of the LAr, or gas-phase cooling. However, if the heat-exchange gas is Ar or N₂, there may still be the “inverse” solubility problem: these gases may dissolve *into* the hydrocarbon to an appreciable degree. Of course, if one can irradiate at LHe temperatures, there should be no problem with melting points and/or solubility for any of the hydrocarbons.

3 Chemical doping

In general, the “chemical” doping method may be divided into the following categories according to the physical approach:

- *Gas-phase mixing.* The matrix material is mixed with a stable paramagnet, with both in gas phase, and the mixture is condensed and solidified directly at sufficiently low temperature, bypassing the liquid state. This method is closely akin to the above photolysis and RF discharge methods. The difference in this case is that the paramagnet is a species stable at ordinary temperatures for times long enough to permit the necessary handling.
- *Liquid-phase mixing.* In this case a stable paramagnet is dissolved into the liquid-phase matrix material and the mixture subsequently frozen. The paramagnet may be a liquid at the mixing temperature, but typically it is a solid.
- *Liquid-phase reaction.* A nonparamagnetic species is dissolved into the liquid-phase matrix material and a chemical reaction creates stable paramagnets in the solution, which is then frozen.
- *Co-crystallization from solution.* Here, both the stable paramagnet and the matrix material are dissolved in a common solvent and the doped matrix is obtained by crystal growth from the solution.
- *Solid-phase diffusion.* In this method a stable paramagnet is brought into contact with the solid-phase matrix material and the paramagnet diffuses into the matrix. The paramagnet may be solid, liquid, or gas. Similarly, a solid-phase reaction might be used.
- *Ion implantation.* Here, stable paramagnetic ions are accelerated into the solid matrix.

In each of these processes, the term "stable" relates to the context of the process. The paramagnetic species may be indefinitely stable in free form at ambient conditions, or it may have a finite lifetime at ordinary conditions, becoming indefinitely stable only in the final low-temperature end product. In general, fewer types of paramagnet are stable enough to be used in chemical doping than in radiolytic doping, mainly because of the higher temperatures that are usually required. This is one of the comparative disadvantages of the chemical method. On the other hand, with chemical doping there exists much greater control of the type and concentration of the dopant.

The classical polarized target material, lanthanum magnesium double-nitrate doped with neodymium (LMN-Nd), was produced by co-crystallization of lanthanum and neodymium salts from water solution. In this case, the associated crystalline water of hydration was the only part of the matrix useful for proton targets. Some of the more modern materials are produced by liquid-phase reaction, e.g., diols are reacted with dissolved inorganic dichromate salts to form metastable Cr^{V} paramagnetic complexes. In this case the preponderant unreacted diol serves as the matrix. Other modern materials are produced by liquid-phase mixing, e.g., the stable free radical porphyrin oxide dissolved in alcohols and the organic-acid-derived stable free forms of Cr^{V} dissolved in alcohols and diols.

3.1 Past attempts to dope hydrocarbons chemically for DNP

A larger amount of effort has been expended on obtaining DNP in hydrocarbons with chemical doping than with radiolytic doping. Most of the attempts have used the liquid-phase mixing approach, because of its relative simplicity. It is fair to say that much of the work has gone unpublished owing to poor results, although in a few cases negative results have been conscientiously reported. I will not try to be exhaustive but simply list here some of the attempts that I know of that seem more interesting, either because they are representative of some class of material or approach, because relatively large values of DNP were achieved, or because they suggest techniques that might be worth further exploration. Again, the list is in order of increasing relative hydrogen content.

Polystyrene

Proton polarizations of 22% have been reported in polystyrene (CH) at 1.2 K, 2.5 T [9]. The dopant was the stable free radical 2,2-diphenyl-1-picrylhydrazyl (DPPH), which was dissolved in ethylene dichloride along with polystyrene, and the solvent was subsequently evaporated from the mixture. This is essentially a co-crystallization type of approach, although bulk polystyrene has little crystalline character. (In fact, this may be the reason that some modest success was achieved, although it was not so realized at the time. See below.)

Toluene

The earliest report of sizable DNP ($\approx 30\%$) in toluene (C_7H_8) is that of Wagner and Haddock [10], at 1.0 K, 2.04 T. The approach was liquid-phase mixing of DPPH. Later measurements of this system gave polarizations of $\approx 50\%$ at 0.5 K, 2.5 T [11]. This same author achieved $\approx 60\%$ polarization with the stable free radical di-tert-butyl nitroxyl (DTBN). Also using DTBN, but with a dilution refrigerator (DR) at 2.5 T, Penttilä *et al.* [12] achieved $\approx 70\%$ polarization. (This was in ^{13}C -enriched toluene.) A polarization of $\approx 25\%$ has been observed [13] at 0.5 K, 2.5 T using the stable free radical sodium bis[2-ethyl-2-hydroxybutanoato-(2-)]oxochromate(V) (EHBA- Cr^V), with a small amount of a crown ether admixed in order to "solubilize" this complex in toluene. This last case is interesting for two reasons: (1) it showed that EHBA- Cr^V , ordinarily not soluble in nonpolar solvents like the hydrocarbons, can be made soluble at least in aromatic-type nonpolar solvents, and (2) the author noted that this sample had inadvertently been allowed to crystallize prior to the DNP measurement. Had this not happened, I do not doubt that the polarization would have been considerably larger. This test was never repeated. (See below.)

Waxes

Samples of "Parowax" (CH_2) doped with DTBN have been polarized to 20–30% at 1.0 K, 2.5 T [14]. The samples were prepared by liquid-phase mixing at a temperature just above the melting point of the wax.

Polyethylene

A proton polarization of 50% has been reported [15] in polyethylene (CH_2) doped with the stable free radical 2,2,6,6-tetramethylpiperidine-1-oxyl (closely related, structurally, to DTBN). The polarizing conditions were not cited, but this was probably at 0.5 K, 2.5 T. The approach was solid-phase diffusion. This is the only example that I know of in which this approach has been used with some success.

Squalane

In 1973, I obtained proton polarizations of $+55/-46\%$ in squalane ($C_{30}H_{62}$) doped with DTBN, at 0.5 K, 2.5 T. The approach was liquid-phase mixing. (Squalane is a heavily-branched alkane, liquid at room temp., m.p. $-38^\circ C$.) These data were never published.

3-Methylpentane

I have a hazy recollection of obtaining DNP of 20% or so in 3-methylpentane (C_8H_{14}) sometime around 1969. (I recently discarded many of my notes from those early years.) If so, the approach would have been liquid-phase mixing of DTBN, the conditions would have been 1.0 K, 2.5 T, and the samples would have been "bagged" in FEP film rather than in bead form, as was the practice at that time. Even if my recollection is wrong, this sort of result would be quite plausible given what we now know. (See below.)

Ethane

Sometime around 1970, Hwang [16] did an experiment in which he mixed DTBN vapor with gaseous ethane and froze the mixture at LHe temperature (gas-phase mixing). He subsequently observed the presence of N^{14} -triplet hyperfine structure (hfs) in the EPR of the solid, indicating that he had probably achieved a good physical dispersion of the DTBN by this method. (If the DTBN had aggregated or “clustered” in the solid phase, one would have expected exchange effects to have “washed out” the discrete hfs.) To my knowledge, this observation has never been followed-up with DNP tests.

3.2 Possible candidates for future work

Perhaps the principal reason that higher polarizations than the above have not been achieved in hydrocarbons is that our “favorite” paramagnets (Cr^V complexes) are not soluble in these nonpolar solvents. As mentioned above, one can, with crown ether additives, attain sufficient solubility in aromatic solvents, but these are inherently less rich in hydrogen than saturated hydrocarbons. We may consider increasing the hydrogen content of toluene by adding a number of $-CH_2-$ groups to it. For example, 1-phenyltetradecane ($C_{20}H_{34}$) is barely still liquid at room temperature (m.p. $16^\circ C$), but even with that large number of CH_2 ’s added, the hydrogen content is only 12.5 wt%. Moreover, the complexing ability of the crown ether would likely be diminished for such an increase in aliphatic character.

On the other hand, the few stable free radicals (notably nitroxyls such as DTBN) that do have reasonable solubility in the alkanes seem to yield DNP-values that are just short of being competitive with those of the Cr^V -doped alcohols, etc. In fact, the arrival on the scene during the 1970’s of diol-, alcohol-, and ammonia-type targets in which polarizations of 80% are readily achieved was a factor in the general lessening of interest in, and the spending of scarce resources on, research on the hydrocarbons. However, it seems possible to me that polarizations approaching 80% in the alkanes are not beyond reach, using DTBN or related radicals, if we were to fully apply all of the techniques and knowledge that are now available. Note that, in every example in the previous section, not all of the following techniques were simultaneously applied:

- The use of DR-cooling.
- The use of frequency-modulation of the microwaves. (We now know that this often improves the polarization.)
- The use of the bead form to improve heat transfer.
- The use of magnetic fields differing somewhat from 2.5 T. (Although it appears that DNP with Cr^V may be near optimal at 2.5 T, there is absolutely no reason to suppose that it is optimal for DTBN.)

Since the inherent figure of merit of some of the light alkanes exceeds that of existing materials (see below), it is also true that they would be competitive at somewhat lower polarization values.

Another reason for the relative lack of success with hydrocarbons is that our "favorite" chemical doping methods, liquid-phase reaction and liquid-phase mixing, are usually successful only if the matrix material readily forms a glass, so that, upon freezing, the desirable property of disorder of the liquid solution (random spatial distribution of the paramagnets) is carried over to the solid state. If the matrix crystallizes, the chances are good that the dopant will be rejected from the lattice as it forms and end up as separate aggregates macroscopically interspersed at the boundaries of crystal domains. This elementary fact has been known to physical chemists and materials scientists for a very long time, but its significance only dawned on us "polarizers" slowly over the course of the 1970's. It so happens that, of the examples in the last section that relied on liquid-phase mixing, all are either easy glass-formers (polystyrene, toluene, squalane, 3-methylpentane) or low-crystallinity polymers (waxes). On the other hand, many hydrocarbons do not vitrify readily. In particular, some of the most hydrogen-rich hydrocarbons, the light alkanes such as methane, ethane, propane, and butane, are probably poor glass-formers, at least in pure form. But we also now know that the admixture of a relatively small amount of some second substance to the matrix material can sometimes convert a recalcitrant substance into an easy glass-former, and I think that some of the light alkanes might respond to this technique.

A third reason for difficulty with the hydrocarbons, at least the most hydrogen-rich ones, is that the melting points tend to be rather low, which complicates the necessary processing and handling. However, if the motivation were sufficiently strong such problems could obviously be overcome. That only takes engineering!

In the process of trying to guess at which possible future efforts might prove the more productive, once again I will use some selection principles to help narrow the focus. First, I will concentrate on the liquid-phase mixing approach, since it is the simplest and probably would require the least in the way of new apparatus and new learning. In turn, this implies that I focus on the issue of glass formation. Second, any new target material, in order to be very interesting, should have the highest possible relative content of hydrogen. Since I know from prior investigations that the alkane isopentane (C_5H_{12}) is an easy glass-former, I can confine the search for other possible glasses to open-chain alkanes with number of carbons ≤ 5 . I am fairly sure, in fact, that isopentane is the *only* open-chain alkane with $n_C \leq 5$ that readily vitrifies in pure form. Therefore, if I hope to make use of the greater hydrogen content of the lighter ($n_C < 5$) alkanes, I should look for "vitrifying additives" for these substances. This could open up a fairly wide and unmanageable territory, so I will limit my considerations here to the straightforward and not unreasonable

Table 1: Thermophysical properties of open-chain alkanes with $n_C \leq 5$.

A ^a	e	F.W.	$T_{m.p.}$ (K)	HR^{-1} (K)	$\rho(\text{solid})$ (g/cm ³)	n.b.p. (K)	T_g (K)
Methane	(CH ₄)	16.04	90.6	112.7	0.519 [90 K]	109.2	
Ethane	(C ₂ H ₆)	30.07	89.8 ^a	344	0.698 [90 K]	184.6	
Propane	(C ₃ H ₈)	44.10	85 ^b	424	(0.74) [85 K]	231	
n-Butane	(C ₄ H ₁₀)	58.12	134.8	561	(0.79) [77 K]	273	
Isobutane	(C ₄ H ₁₀)	58.12	113.8	555	(0.78) [77 K]	261	
n-Pentane	(C ₅ H ₁₂)	72.15	143.4	1013	(0.82) [77 K]	309	
Isopentane	(C ₅ H ₁₂)	72.15	113.2	619	0.816 [77 K] ^c	301	65 ^d
Neopentane	(C ₅ H ₁₂)	72.15	256.4	392	(0.81) [77 K]	283	

^aSee text.

^bAverage of several sources.

^cAuthor's measurement.

^dRef. [18, p. 6].

situation in which the alkanes serve as vitrifying additives for each other, i.e., I consider mixtures of open-chain alkanes with $n_C \leq 5$. Lastly, I am going to exclude methane from the picture, since I feel that its small relaxation time makes it a poor candidate.

It is by now well known that the mixtures that have the best chance of ready glass formation are eutectic mixtures [17][18]. I don't have at hand any published experimental information on the phase diagrams of mixtures of these alkanes (although such literature must surely exist). In order to make some initial quick estimates I will calculate the binary eutectic compositions assuming ideal binary mixtures. Rastogi [19] gives simple formulas for this case. If we let T_i be the melting points of the two ($i = 1, 2$) pure components and H_i be the corresponding heats of fusion, then the mole fraction x of component 2 and the melting point T_e of the eutectic mixture satisfy the relations [19, Eqs. (36) and (37)]

$$x + e^{H_1 R^{-1}(T_1^{-1} - T_2^{-1})} x^{H_1 H_2^{-1}} = 1, \quad (1)$$

$$T_e = (T_2^{-1} - R H_2^{-1} \ln x)^{-1}, \quad (2)$$

where $R = 8.314 \text{ J/mol}\cdot\text{K}$ is the gas constant.

Table 1 lists the thermophysical data needed to solve Eqs. (1) and (2), along with some other related information, for the materials of interest. (Methane is included here for the sake of completeness.) Here, ρ is density, n.b.p. is "normal boiling point," and T_g is the glass transition temperature. Except as noted, the data are

Handbook values. The melting point listed for ethane is actually the temperature of the solid-solid transition that is known [20] to exist just below the true melting point, and the heat of fusion includes that of this transition. The densities given in parentheses are my own estimates for those cases that I couldn't readily locate.

Table 2 gives the estimates of eutectic composition resulting from Eqs. (1) and (2) for various binary combinations. Also included for comparison at the bottom of the table are the corresponding data (where relevant) for pure isopentane, 3-methylpentane, ammonia, and the best of the "standard alcohol" target materials, 1-pentanol/water. In Table 2, the Effective Formula expresses the composition of the mixture in terms of a fictitious 1-carbon molecule for ease of computation. Aside from ammonia, the entries are arranged in order of decreasing relative hydrogen content. The ratio T_e/T_1 is a measure of the estimated depression of the melting point, and has the following significance: mixtures in which the melting point is more strongly depressed (smaller ratio) should be more favorable for glass formation, although quantitative distinction is difficult. For this reason, and in order to slightly trim down the table, I have omitted five of the possible mixtures for which $T_e/T_1 > 0.98$. The quantity $T_g(\text{est.})$ is the estimated glass transition temperature, $T_g(\text{est.}) \approx 0.6T_e$. (T_g can be thought of as the softening, or "melting," point of a glass, from a rather simplistic point of view. Remember that T_e is the true melting point of the *crystalline* form of the mixture.) I have estimated the solid density of each mixture, $\rho(\text{est.})$, by combining the densities of the two components in the same ratio as the mole fractions. The quantity ρ_T would be the overall density when used as a target material,

$$\begin{aligned}\rho_T &= 0.65\rho(\text{est.}) + 0.35\rho_{\text{LHe}} \\ &= 0.65\rho(\text{est.}) + 0.049 \text{ g/cm}^3,\end{aligned}\tag{3}$$

where $\rho_{\text{LHe}} = 0.14 \text{ g/cm}^3$ is the density of LHe, and the coefficients correspond to a volume packing fraction of 0.65, which is typical for polarized targets. Similarly, the overall hydrogen density, ρ_H , is obtained by multiplying the hydrogen density of the bulk material by 0.65. Some of the numerical results have been carried to more digits than warranted by the inputs, to reduce rounding errors.

The last two entries in Table 2 are figures of merit for the materials:

$$\begin{aligned}F &= \rho_T(\rho_H/\rho_T)^2 \times 10^4 \\ &= \rho_H^2/\rho_T \times 10^4,\end{aligned}\tag{4}$$

$$F_{ct} = (\rho_H/\rho_T)^2 \times 10^4,\tag{5}$$

where F is the standard HEP figure, corresponding to the situation in which the beam length of the target is limited by the target refrigerator's dimensions, and F_{ct} is the constant-thickness figure, corresponding to the situation in which the beam length is limited by the scattering physics. (I believe that the second figure

Table 2: Properties of the estimated eutectic mixtures.

Eutectic mixture	x (mol %)	Effective Formula	T_e (K)	T_e/T_1	T_g (est.) (K)	ρ (est.) (g/cm ³)	ρ_T (g/cm ³)	ρ_H (g/cm ³)	F (g/cm ³)	F_{α}
Alkane(1)/alkane(2)										
Ethane/n-butane	10.4	CH _{2.906}	87.3	0.972	52	0.708	0.509	0.0902	160	314
Ethane/isobutane	19.2	CH _{2.838}	85.0	0.947	51	0.714	0.513	0.0893	155	302
Ethane/isopentane	17.1	CH _{2.796}	85.6	0.953	51	0.718	0.516	0.0887	152	296
Propane/ethane	47.6	CH _{2.792}	75.3	0.886	45	0.720	0.517	0.0888	153	295
Propane/isobutane	15.4	CH _{2.634}	82.2	0.967	49	0.746	0.534	0.0878	144	270
Propane/isopentane	13.2	CH _{2.613}	82.6	0.972	50	0.750	0.536	0.0877	143	267
Isobutane/n-butane	31.6	CH _{2.500}	105.6	0.928	63	0.783	0.558	0.0883	140	250
Isobutane/n-pentane	12.5	CH _{2.485}	110.8	0.974	66	0.785	0.559	0.0880	139	248
Isobutane/neopentane	13.3	CH _{2.484}	110.5	0.971	66	0.784	0.559	0.0879	138	247
n-Butane/neopentane	21.3	CH _{2.475}	127.5	0.946	76	0.794	0.565	0.0888	139	247
n-Butane/n-pentane	31.9	CH _{2.463}	123.4	0.915	74	0.800	0.569	0.0891	139	245
Isobutane/isopentane	48.8	CH _{2.446}	100.1	0.880	60	0.798	0.568	0.0883	137	242
Isopentane/n-butane	31.9	CH _{2.427}	105.8	0.935	63	0.808	0.574	0.0889	137	239
n-Pentane/neopentane	26.6	CH _{2.400}	137.4	0.958	82	0.817	0.580	0.0890	137	235
Isopentane/n-pentane	12.3	CH _{2.400}	110.5	0.976	66	0.816	0.579	0.0889	136	235
Isopentane/neopentane	13.2	CH _{2.400}	110.3	0.974	66	0.815	0.579	0.0888	136	235
Pure isopentane	—	CH _{2.400}	—	—	65	0.816	0.579	0.0889	136	235
3-Methylpentane	—	CH _{2.333}	—	—	≈77	0.842	0.596	0.0896	135	226
Ammonia	—	NH ₃	—	—	—	0.830	0.588	0.0958	156	265
1-Pentanol/water	≈23.1	CH _{2.520} O _{0.260}	≈190	—	≈125	0.966 ^a	0.677	0.0853	107	159

^aRef. 21.

is relevant to LAMPF E-1256.) The figure of merit is inversely proportional to the running time required to attain a given level of statistical error. The figure for the entire polarized target would have to also include the effects of extraneous background and the square of the actual polarization as a factor. The factors above are computed as if the polarization were 100%.

The basic conclusion to be drawn from Table 2, which was perhaps obvious from the start, is that all of the hydrocarbons listed have figures that are potentially better than that of pentanol/water, and some are better than ammonia. Of course, the polarization that can actually be achieved is a key question. It is interesting to note that, relative to pentanol/water at 80% polarization, the ethane/butane mixture would break even at a polarization of only 57% in the constant-thickness case. Another point to notice is that most of the T_g 's are well below LN_2 temperatures. Only pentane/neopentane, 3-methylpentane (and the similar 2-methylpentane, $T_g \approx 80$ K, which is not tabulated), and perhaps butane/neopentane and butane/pentane would be "workable" hard glasses at 77 K. The other materials would have to be "beaded" and loaded into the refrigerator at lower temperatures. This is a practical problem of some magnitude, and I do not mean to minimize it by my previous remarks. In regard to bead preparation, the use of a liquid neon (LNe, n.b.p. 27 K) bath is a possibility. I believe LNe is not very expensive and has a sufficiently high latent heat of vaporization that it can be held in ordinary glass dewars for reasonable working times. However, the fact that the density of LNe is $\approx 1.2 \text{ g/cm}^3$ is a potential drawback, since the beads will permanently float.

Finally, to return to some of the major issues of this section, it should be emphasized that there is no guarantee that all of the eutectics of Table 2 would be easy glass-formers, nor that a free radical such as DTBN would be sufficiently soluble in them. My feeling about the second question is that there is no problem, except possibly for those cases in which the n.b.p. is < 250 K. Regarding the first question, it is quite certain that *at least one* of the mixtures will readily vitrify. I have recently found a reference to a mixture of isobutane/isopentane as a glass-former [22]. This raises my level of optimism considerably.

4 Conclusion

This note contains a number of suggestions, either explicit or implied, for future work. Since we must always attempt to match the degree of difficulty with the level of our ambition and resources, I will try to identify the paths of least resistance:

1. If I were going to try radiolytic doping, I would probably start with neopentane. It has a very high melting point, for ease of handling, and a correspondingly low probability of co-solubility problems with the coolants. Also,

its structure is so symmetrical that it is unlikely that diverse paramagnetic species would be produced. My second choice would be n-butane.

2. For chemically-doped hydrogen targets, I would start with tests of either 2- or 3-methylpentane doped with DTBN. These are room-temperature liquids with T_g 's just high enough to make fairly hard glasses at 77 K, and probably have little co-solubility with N_2 . If the results seemed encouraging, I would move on to try some of the higher- T_g mixtures noted above that might have high enough viscosity at 77 K. Finally, if suitably encouraged, I would try to work out methods for handling the low- T_g mixtures, and for checking on the solubility of DTBN in them. Before doing DNP tests on *any* of the two-component mixtures, I would do benchtop microcalorimetry on the mixtures to quickly establish the eutectic points and glass-formation potentials. (Calorimetry runs are ten times less time-consuming and expensive than DNP runs.) It is important to note that, even though one may obtain a reasonable-looking glass phase with mixtures that are not close to the eutectic, previous experience with non-hydrocarbons suggests that the best DNP results are obtained right at the eutectic composition.
3. If I were interested only in good ^{13}C -targets, I would "revisit" toluene doped with crown ether and $EHBA-Cr^V$ with a more careful DNP test than the one described in Sec. 3.1.

Microwave-FM capability should be available for any DNP tests, otherwise, an inexpensive gain may be missed. On the other hand, DNP trials at fields other than 2.5 T, although potentially valuable, are much more expensive unless one has access to an existing apparatus with this capability. Likewise, a search for soluble radicals, other than DTBN, could be very time-consuming. (I have considered some low-m.p. species like NO and NO₂ [23], and ClO₂ [24], but these don't look very hopeful. The first two seem to prefer to dimerize (lose paramagnetism) in the solid state, and ClO₂ is potentially explosive.)

A final word about nuclear spin isomerism is in order. Most of us are familiar with the spin isomerism associated with homonuclear diatomic molecules, such as the *ortho/para* isomers of H₂. That isomerism takes a particularly simple form because the rotation *permutation* operator is equivalent to the *parity* operator in the ground electronic state. In polyatomic systems or quasi-isolated molecular groups in which the rotation permutations are less simple, the Pauli principle requires more complex couplings of spin- and space-wavefunctions, and, if the systems are embedded in a condensed solid, the environment further affects the spectrum of states. For example, CH₄ has three isomers $A(m=2)$, $T(m=1)$, and $E(m=0)$, where m is the total spin projection of its four protons. In the low-temperature solid, 1/4 of the molecules exist as nearly free rotors with angular momentum-isomer pairings

$J = 0, A$; $J = 1, T$; $J = 2, T + E$; etc. The rest of the molecules exist on a separate sublattice and are rotationally hindered so that the ground state is librational, and "rotation" at low temperatures proceeds only via quantum tunneling. The free-rotor states bear some similarity to those of H_2 , with a splitting between $J = 0$ and $J = 1$ levels of 1.07 meV (12.4 K, or 259 GHz). The degenerate ground tunneling states, by contrast, are split by nuclear dipole interactions into A, T , and E isomeric sublevels with much smaller splittings, e.g., $A \rightarrow T = 145 \mu\text{eV}$ (1.7 K, or 35 GHz) [25]. For methane in the neighborhood of 1 K, the spin physics is thus rather complex. In general, spin isomerism and associated tunneling can lead to various complications in the interpretation of NMR measurements, including nonexponential relaxation [26], spin-isomer conversion over time [27], time- and temperature-dependence of the resonance lineshape, and deviation of the magnetization from the Curie law [28]. This last possibility is perhaps the most worrisome for target applications, where the Curie law is relied upon for the thermal equilibrium calibration constant.

Fortunately, at least for our purposes here, it appears that the alkanes larger than methane are more well-behaved than methane. In these molecules the only significant low-temperature rotations are those of the methyl ($-CH_3$) groups. Methyl groups have two spin-isomers $A(m = 3/2)$ and $E(m = 1/2)$. The rotation of the group is almost always hindered to some appreciable degree since it is usually attached to some larger structure, but tunneling states are still possible and the effects of the tunneling are, in fact, measurable in the NMR of many low-temperature solids. In a few cases tunneling splittings > 1 K have been found. However, the tunneling splitting for the methyl groups in solid propane, for example, is only ≈ 80 kHz ($3.8 \mu\text{K}$) [29], and in n-butane it is probably not much more than 100 kHz ($4.8 \mu\text{K}$) [30]. I have no information for ethane, but, unless the whole molecule has a low rotation barrier, which I doubt, the splitting is probably not a great deal larger. The only effects of these small splittings would be some narrowing of the NMR line and, possibly, some nonexponential admixture to the decay curve of the polarized signal if splittings as large as 10 MHz (0.48 mK) or so are somehow present. In particular, assuming that the splittings in glassy forms would not differ greatly from these crystalline values, I expect the Curie law to be valid down to 1 K for the materials of interest [31]. (It is informative to compare the above splittings to those in NH_3 (≈ 60 kHz) [32] and alcohols (≈ 5 kHz) [33].) Nevertheless, if an investigation of these materials is undertaken one should be on the lookout for the unexpected.

I have collected the information in this note haphazardly over a long time period. I am sure that a methodical literature search would produce further useful references to the properties of the light hydrocarbons, especially in the following areas: radiolytic doping, solubility with Ar and N_2 , phase diagrams and eutectic points of the mixtures, glass formation, and densities of the low temperature solids. I believe that M. Krumpolc is well-placed to do such searches, and he should be encouraged to do so.

References

- [1] W. Th. Wenckebach, *Helv. Phys. Acta* **59** (1986) 737; H. W. van Kesteren, W. Th. Wenckebach, and J. Schmidt, *Phys. Rev. Lett.* **55** (1985) 1642.
- [2] D. A. Hill, B. A. Hasher, and C. F. Hwang, *Phys. Lett.* **23** (1966) 63.
- [3] M. L. Seely *et al.*, *Nucl. Instrum. Methods* **201** (1982) 303.
- [4] S. Trentalange *et al.*, in *Proc. 9th Int. Symp. on High Energy Spin Physics*, eds. W. Meyer *et al.* (Springer-Verlag, Berlin, 1991), Vol. 2, pp. 325–327.
- [5] S. Ya. Pshezhetskii *et al.*, *EPR of Free Radicals in Radiation Chemistry* (Halsted Press, New York, 1974) [trans. Keterpress Enterprises, Jerusalem, Israel].
- [6] H. Glättli, in *Proc. of the Second Workshop on Pol. Target Mat.*, eds. G. R. Court *et al.* (Rutherford, RL-80-080, 1980), pp. 46–48.
- [7] For example, see H. Glättli, P. Calvani, and B. Bouchet, *J. Chem. Phys.* **85** (1986) 671, and references therein.
- [8] E. Szczepaniec-Cięciak, V. A. Kondaurov, and S. M. Melikova, *Cryogenics* **20** (1980) 48.
- [9] C. F. Hwang *et al.*, *Nucl. Instrum. Methods* **51** (1967) 254. This was an extension of previous work reported by T. J. B. Swanenburg *et al.*, *Physica* **29** (1963) 713.
- [10] R. J. Wagner and R. P. Haddock, *Phys. Rev. Lett.* **16** (1966) 1116.
- [11] R. Fernow, *Nucl. Instrum. Methods* **159** (1979) 557.
- [12] S. Penttilä *et al.*, in Ref. [4], pp. 315–319.
- [13] D. Crabb, in Ref. [6], pp. 52–54.
- [14] A. Moretti *et al.*, *Rev. Sci. Instrum.* **38** (1967) 1335.
- [15] E. I. Bunyatova, in Ref. [4], pp. 333–339.
- [16] C. F. Hwang, private communication.
- [17] J. J. Gilman, *Science* **208** (1980) 856; M. H. Cohen and D. Turnbull, *Nature (London)* **189** (1961) 131.
- [18] For a highly readable introduction to the phenomena of the glass-state, eutectics, and related esoterica, see the first chapter of R. Zallen, *The Physics of Amorphous Solids* (John Wiley and Sons, New York, 1983).
- [19] R. P. Rastogi, *J. Chem. Educ.* **41** (1964) 443.
- [20] H. M. Roder, *J. Chem. Phys.* **65** (1976) 1371.
- [21] S. Takala and T. O. Niinikoski, in Ref. [4], pp. 347–352.
- [22] T. Wakayama *et al.*, *J. Phys. Chem.* **74** (1970) 3584.

- [23] C. K. Jen *et al.*, *Phys. Rev.* **112** (1958) 1169; F. J. Adrian, B. F. Kim, and J. Bohandy, *J. Chem. Phys.* **82** (1985) 1804; M. Zomack and K. Baberschke, *Phys. Rev.* **B36** (1987) 5756.
- [24] N. Ohta and K. Kuwata, *J. Chem. Phys.* **82** (1985) 3420.
- [25] For a recent paper on spin isomerism in methane, see B. Asmussen *et al.*, *J. Chem. Phys.* **97** (1992) 1332.
- [26] For example, see P. Coppens *et al.*, *Phys. Rev.* **B33** (1986) 7494.
- [27] For example, see A. Buekenhoudt, G. Vandemaele, and L. Van Gerven, *Phys. Rev.* **B41** (1990) 9038.
- [28] For example, see S. Emid and R. A. Wind, *Physica* **93B** (1978) 344.
- [29] J. A. Ripmeester, S. K. Garg, and D. W. Davidson, *J. Chem. Phys.* **67** (1977) 2275.
- [30] M. J. R. Hoch, *J. Chem. Phys.* **65** (1976) 2522.
- [31] G. Vandemaele, P. Coppens, and L. Van Gerven, *Phys. Rev. Lett.* **56** (1986) 1202.
- [32] D. E. O'Reilly, E. M. Peterson, and S. R. Lammert, *J. Chem. Phys.* **52** (1970) 1700.
- [33] C. Mottley *et al.*, *J. Chem. Phys.* **61** (1974) 1078.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

**DATE
FILMED**

1 / 29 / 93