RECEIVED
USDOE/PETC

DOE/PC/91301--6

DE93 012286

93 APR -5 PM 1:04

ACQUISITION & ASSISTANCE DIV.

ETHANOL SYNTHESIS AND WATER GAS SHIFT OVER BIFUNCTIONAL SULFIDE CATALYSTS

OSTI

Technical Progress Report for the Period
December 1992-February 1993

Kamil Klier
and
Richard G. Herman
with
Michael Deemer

Zettlemoyer Center for Surface Studies
and Department of Chemistry
Lehigh University
Bethlehem, PA 18015

March 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PREPARED FOR THE UNITED STATES
DEPARTMENT OF ENERGY-Pittsburgh Energy Technology Center

Under Contract No. DE-FG22-91PC91301

U.S.-DOE Patent Clearance is not required prior to
publication of this document.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ETHANOL SYNTHESIS AND WATER GAS SHIFT OVER BIFUNCTIONAL SULFIDE CATALYSTS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

ETHANOL SYNTHESIS AND WATER GAS SHIFT OVER BIFUNCTIONAL SULFIDE CATALYSTS

SUMMARY OF TECHNICAL PROGRESS

During this quarter, high pressure (8.1 MPa) and high temperature (up to 350°C) catalytic testing was carried out with a 10 wt% cesium doped molybdenum disulfide for 188.5 hr. The doping of the catalyst was carried out under vacuum, instead of evaporating a methanolic solution of cesium formate. This procedure proved to initially provide an active catalyst, although the catalyst was not as active as previously reported [1] for a similarly prepared catalyst. Upon prolonged testing, deactivation of the catalyst was observed. Surprisingly, the selectivity pattern was reversed from that of the fresh catalyst, i.e. the alcohol synthesis selectivity increased with increasing reaction temperature rather than decreased. The causes of this deactivation and selectivity reversal have not yet been determined, but characterization studies are underway with this catalyst.

ETHANOL SYNTHESIS AND WATER GAS SHIFT OVER BIFUNCTIONAL SULFIDE CATALYSTS

TECHNICAL PROGRESS

Catalyst Preparation and Doping Procedures:

The same batch of molybdenum disulfide was used in this study as for the catalysts previously tested. This MoS_2 sample has a surface area of $60 \text{ m}^2/\text{g}$. A different alkali doping method was used, in which the impregnation was carried out under vacuum. A 0.2339 M aqueous solution of cesium formate was prepared. This was made by weighing out 4.0488 g of 99.9% cesium formate and diluting it to 100 ml with distilled water. For a 10% doping level, 3.32 ml of the 0.2339 M solution was needed. The 3.32 ml portion was then diluted with distilled water to approximately 40 ml .

The diluted cesium formate solution was introduced using a vacuum system as is pictured in Figure 1 [2]. The molybdenum disulfide (1.2100 g) was placed in the flask, and the apparatus was connected to the vacuum manifold. The sample and the apparatus were evacuated at 105°C for 2 hr and then cooled to room temperature. Using a syringe, 10 ml of the diluted CsOOCH solution was added to the MoS_2 . This was heated to 60°C under vacuum, and the solid was allowed to go to dryness. This was repeated until all of the CsOOCH solution (40 ml) was added. The apparatus was then detached from the manifold, and the $10\% \text{ Cs/MoS}_2$ catalyst was scraped from the flask. After detachment from the vacuum system, no effort was made to exclude air from the sample.

Catalytic Testing:

A 1.1290 g portion of the $10\% \text{ Cs/MoS}_2$ catalyst was mixed with approximately 15 ml of 3 mm Pyrex beads. This mixture was then centered in a 316 stainless steel fixed bed

reactor using additional quantities of the 3 mm Pyrex beads. The loading of the catalyst into the reactor was carried out in air. After the reactor was reassembled, the catalyst was pretreated at 410°C for 1 hr under a flow of 2.04/97.96 H₂/N₂ vol% mixture at a flow rate of 60 ml/min. The reactor was then allowed to cool to room temperature overnight while maintaining the hydrogen/nitrogen flow. The gas flow was then changed to the H₂/CO = 1 synthesis gas reactant mixture, and the reactor was pressurized to 8.1 MPa, the gas hourly space velocity (GHSV) was adjusted to 7750 ℓ/kg cat/hr, and then heated at a steady rate to the initial reaction temperature.

Catalytic testing was carried out at two sets of temperatures. The first set consisted of the series 245, 256, 285, 295, 300, 308, 310, and 350°C. The second temperature set consisted of 265, 275, 288, 340, 285, and 245°C. The second set of temperatures was run directly after the first set of temperature. As will be shown in the figures in this report, there was a difference between the two sets of temperatures. This indicated that the catalyst deactivated over time. This was especially pronounced after lowering the temperature to 245°C at the end of the second temperature sequence. Indeed, while there was activity at this temperature at the beginning of the testing sequence, there was no activity observed at the end of the second reaction series that terminated at 245°C. The testing at each temperature was maintained at steady state for 6-24 hr. The catalytic response to a temperature change was immediate.

Some of the observed general catalytic trends are summarized here. As expected, the selectivity of the alcohols decreased as the temperature increased, while the selectivity of the hydrocarbons increased as the temperature increased for Temperature Set 1. These trends are shown in Figures 2 and 3. This behavior, however, was surprisingly not observed during the Temperature Set 2 testing sequence. As shown in Figures 4 and 5, the selectivity

trends were now reversed, with the selectivity towards alcohols improving as the temperature was increased. In each case, the selectivities were calculated on a CO- and CO₂-free basis.

Space time yields and % yields of the products are shown in Figures 6-14. With respect to the hydrocarbons, the C₂ % yield and space time yield increased with temperature as expected as seen in Figures 10 and 11, respectively. The methane % yield and space time yield also increased with increasing temperature as expected as shown in Figures 8 and 9, respectively. However, unexpectedly no detectable methane was produced at low temperature while a substantial amount of C₂ hydrocarbon was produced. The CO₂ space time yield (Figure 12) increased with increasing temperature. The alcohol % yields and space time yields were somewhat erratic in behavior, as indicated in Figures 13 and 14. However, the trends are clearly evident. During the Temperature Set 1 testing, the alcohol % yield tended to approach a constant value as higher reaction temperatures were employed (Figure 13). On the basis of space time yield, a broad maximum in the alcohol productivity was observed (Figure 14) at about 300°C.

During the Temperature Set 2 experiments, the % yield increased with increasing temperature, as shown in Figure 13. Similarly, the overall alcohol productivity also increased with temperature (Figure 14). Thus, the behavior of the catalyst during these two sets of experiments was significantly different. Although there is scatter in the data, the conversion of CO in mol% and mol/kg cat/hr increased with increasing temperature for both series of experiments, as shown in Figures 15 and 16, respectively. The extent of deactivation is indicated in these figures, where the solid lines are computer-drawn trend lines that neglect the final 245°C data point (no activity).

Ethanol tended not to be observed as a product below 285°C. However, at 350°C a substantial amount of ethanol was produced. The hydrocarbon/alcohol molar ratio during

Temperature Set 1 testing increased as the temperature increased. However, under Temperature Set 2 conditions, the ratio decreased as the temperature increased (Figure 17). This latter observation is the opposite of the expected behavior.

Figure 18 shows the results of the 10 wt% cesium doped MoS₂ testing at 295°C in terms of total alcohols, methanol, ethanol, and hydrocarbons formed (solid symbols) as compared to earlier results [1]. It can be seen that the present catalyst is less active than those prepared earlier [1]. However, Figures 6, 11, and 14 indicate that the space time yields of these products are anomalously low compared to the 285, 300, and 310°C testing results. For example, the total alcohol productivities at these temperatures were 136.2, 138.8, and 135.3 g/kg cat/hr, respectively, compared with 92.5 g/kg cat/hr reported in Figure 18 for the current 295°C test. The causes of the lower activity and deactivation over time are being probed by catalyst characterization methods. Future experiments will include electron microscopy of "fresh" and spent catalysts to determine the location and particle size of the cesium dopant. In addition, surface areas will be measured to see if a loss of surface area occurred during the testing procedure, and chemical analysis and X-ray powder diffraction of the samples will also be carried out.

REFERENCES:

1. Klier, K., Herman, R. G., Simmons, G. W., Lyman, C. E., Santiesteban, J. G., Najbar, M., and Bastian, R., "Direct Synthesis of Alcohol Fuels Over Molybdenum-Based Catalysts," Final Technical Report DOE/PC/80014-F, 261 pp (December 1988).
2. Santiesteban, J. G., Ph.D. Dissertation, Department of Chemistry, Lehigh University (1989).

FIGURE 1. Diagram of the Vacuum System

FIGURE 2. Selectivity vs Temperature
(Set 1) at 8.1 MPa and GHSV =
7750 l/kg cat/hr with $H_2/CO = 1$

FIGURE 3. Selectivity vs Temperature
(Set 1) at 8.1 MPa and GHSV = 1
7750 l/kg cat/hr with H₂/CO = 1

FIGURE 4. Selectivity vs Temperature
(Set 2) at 8.1 MPa and GHSV =
7750 l/kg cat/hr with H₂/CO = 1

FIGURE 5. Selectivity vs Temperature
(Set 2) at 8.1 MPa and GHSV =
7750 l/kg cat/hr with $H_2/CO = 1$

**FIGURE 6. Product Space Time
Yield vs Temperature (Set 1) at
8.1 MPa, 7750 l/kg cat/hr, H₂/CO = 1**

**FIGURE 7. Product Space Time
Yield vs Temperature (Set 2) at
8.1 MPa, 7750 l/kg cat/hr, $H_2/CO = 1$**

**FIGURE 8. Methane % Yield vs
Temperature at 8.1 MPa and GHSV =
7750 l/kg cat/hr with $H_2/CO = 1$**

**FIGURE 9. Methane Space Time
Yield vs Temperature at 8.1 MPa and
GHSV = 7750 l/kg cat/hr with $H_2/CO = 1$**

FIGURE 10. C₂ Hydrocarbon % Yield
vs Temperature at 8.1 MPa and
GHSV = 7750 l/kg cat/hr with H₂/CO = 1

FIGURE 11. C₂ Hydrocarbon Space Time Yield vs Temperature at 8.1 MPa and GHSV = 7750 l/kg cat/hr with H₂/CO = 1

FIGURE 12. Carbon Dioxide Space Time Yield vs Temperature at 8.1 MPa and GHSV = 7750 l/kg cat/hr with $H_2/CO = 1$

**FIGURE 13. Total Alcohol % Yield
vs Temperature at 8.1 MPa and
GHSV = 7750 l/kg cat/hr with $H_2/CO = 1$**

**FIGURE 14. Total Alcohol Space Time
Yield vs Temperature at 8.1 MPa and
GHSV = 7750 l/kg cat/hr with H₂/CO = 1**

**FIGURE 15. Conversion Rate
of CO vs Reaction Temperature**

FIGURE 16. Conversion of CO
in Mol% vs Reaction Temperature

FIGURE 17. Hydrocarbon/Alcohol Molar Ratio vs Temperature from $H_2/CO = 1$ at 8.1 MPa and 7750 l/kg cat/hr

FIGURE 18. Comparison of the Current Catalyst with Previously Tested Cs/MoS₂ Catalysts [1,2]

END

DATE
FILMED

5 / 20 / 93