DOE/PC/91311--T3

QUARTERLY PROGRESS REPORT

DOE/PC/91311--T3

ON

DES/2 019869

CONFIGURATIONAL DIFFUSION OF ASPHALTENES IN FRESH AND AGED CATALYSTS EXTRUDATES

Grant No. DE-FG22-91PC91311

3-20-92 to 6-20-92

James A. Guin
A Ray Tarrer

Chemical Engineering Department
Auburn University
Auburn, AL 36849

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

JUL 09 1992

Table of Contents

Objective and Work Statement.....	1
Summary of Progress.....	3
Planned Work.....	3
Detailed Progress.....	4
Literature Review.....	4
Mathematical Intrapore Diffusional Model.....	19
Data Fitting of the Model.....	26

AUG 21 1992

Statement of Work

Configurational Diffusion of Asphaltenes in Fresh and Aged Porous Catalyst Extrudates

Objective: The objective of this research is to determine the relationship between the size and shape of coal and petroleum macromolecules and their diffusion rates i.e., effective diffusivities, in catalyst pore structures. That is, how do the effective intrapore diffusivities depend on molecule configuration and pore geometry.

Task 1. Relationship Between Effective Intrapore Diffusion Coefficients, Molecular Size and Pore Geometry.

Finite bath-type diffusion experiments will be performed using both coal and petroleum-derived macromolecular species, e.g. asphaltenes, as well as model compounds, e.g. porphyrins, polymers, of known molecular size. By monitoring the concentration of solute macromolecules in the bath, the effective intrapore diffusion coefficients will be determined through application of the appropriate diffusion equations. Macromolecular species concentrations will be monitored by size exclusion chromatography (SEC). Relationships will be sought between the size, and shape, e.g. planar, coil, of the diffusing solutes and the pore geometry (pore size distribution) of the catalyst support. The effects of molecule configuration and catalyst pore size distribution on the effective intrapore diffusivity will be examined. Specially prepared laboratory catalysts with very narrow pore size distributions and other model porous media, e.g. porous Vycor glass, will be utilized in the experiments. Pore structures of all catalysts and other porous media will be characterized by mercury porosimetry and surface area (BET) analysis.

Task 2. Effects of Solvent Composition, Solute Concentration, and Temperature on the Molecular Configuration and Diffusion Rate of Coal and Petroleum Asphaltenes in Catalyst Pores.

Diffusion experiments such as in Task 1 will be performed with varying solvent compositions, i.e., paraffinic-aromatic mixtures, to examine the effects of the state of molecular

aggregation (self-assemblies) on the rates of diffusion of coal and petroleum asphaltenes in the catalyst pores. Similar experiments will be performed to study the effect of *temperature* and solute (macromolecule) *concentration* on the state of molecular configuration and aggregation on the resulting pore diffusivity.

Task 3. Assessment of Diffusional Limitations in Aged Catalysts

Diffusivity measurements such as conducted in Task 1 will be performed with both model compound and coal-derived macromolecular species using extrudate-type aged catalysts from laboratory experiments as well as aged catalysts obtained from actual coal liquefaction pilot plants such as the Wilsonville, AL Advanced Coal Liquefaction R & D Facility. From the experimental diffusivities so obtained, an evaluation of effects of changes in catalyst pore structure, e.g. tortuosity, pore plugging, shall be made. The changes in pore diffusivities associated with the pore structural changes caused by coke and metals deposition will be investigated, as compared with the fresh catalysts. An assessment of the relationship of increased diffusional limitations to coke and metals deposition in the catalyst pores will be made based on the results of the diffusivity measurements. The degree to which pore diffusivities can be restored to their original values by carefully controlled oxidation and/or extractive catalyst regeneration techniques also will be explored. The practical importance of these findings to coal liquefaction technology will be evaluated.

Summary

This quarter we made a more comprehensive literature survey concerning configurational diffusion in porous catalysts or catalyst supports. A detailed literature review is reported. Also, a mathematical configurational diffusion model was developed. By using this model, the effective diffusivity for model compounds diffusing in porous media and a linear adsorption constant can be determined by fitting experimental data.

Planned Work

A new PhD student has joined the project, Mr. X. Yang. He has begun his work this quarter. The M.S. student working on the project, Mr. C. C. Chen, graduated in June, 1992. Work next quarter will consist of numerical solution of the mathematical model and some experimental work. Also, a visiting scientist, Dr. C. Y. Chang from National Taiwan University, will join the project for 1 year beginning in August, 1992.

LITERATURE REVIEW

INTRODUCTION

Diffusion in a porous material is very important in heterogeneous catalysis. It is generally recognized that in heterogeneous catalysis, diffusional mass transfer and adsorption reaction processes are through the following basic seven steps:

- (1). external diffusion: the diffusion of reactant(s) from bulk phase through boundary layer to the external surface of catalysts;
- (2). intrapore diffusion: the diffusion of reactant(s) within the pellet pores to the active sites of the catalysts;
- (3). surface adsorption: the adsorption of the reactant(s) on the surface or the active sites of the catalysts;
- (4). surface reaction: the surface catalytic reaction of reactant(s) to produce product(s) on the surface or active sites of the catalysts;
- (5). desorption: the desorption of the product(s) from the surface or active sites of the catalysts;
- (6). intrapore diffusion: the diffusion of the product(s) from the surface or active sites of the catalysts to the internal pores of the catalysts;
- (7). external diffusion: the diffusion of the product(s) from the internal pores to the bulk phase through the boundary layer.

If the rates of adsorption, desorption and surface reaction, or steps 3, 4, 5, are comparably large, then the diffusion steps

could be the rate limiting steps in heterogeneous catalysis. Generally, the external diffusion, that is, steps 1 and 7, can be diminished or improved by some improvement of reaction conditions. Thus, the intrapore diffusion, or the diffusion of reactant and product molecules to and from the catalyst active sites within the pore structure, are frequently the rate limiting steps in heterogeneous catalysis, particularly when the diameters of molecules of reactant and product are comparable to the sizes of the internal pores of the catalyst.

Evidence for the intrapore diffusional influences has been widely observed by investigators as reviewed below. Since a large number of catalytic reactions were carried out in porous catalyst supports, such as zeolites, alumina, silica, knowing the mechanisms of diffusion and evaluating the effective diffusivities in porous materials have great importance to heterogeneous catalysis.

INTRAPORE DIFFUSIONAL PHENOMENA IN POROUS MATERIALS

There is considerable evidence that intrapore diffusional phenomena do exist in porous materials, even when the diameters of the diffusional molecules are comparable to those of the porous materials.

Diffusion in Membranes

Intrapore restricted diffusion was first observed in membrane diffusion. It has been shown⁽¹⁾ that the rates of diffusion of organic molecules through membranes in very small pores decrease as

a function of molecular sizes far more rapidly than can be accounted for on the basis of the molecular diffusion. The decrease in diffusion was directly correlated with the ratio of molecular size to membrane pore size⁽²⁾. Generally, there is no surface diffusion in membranes⁽³⁾.

Diffusion in Zeolites

Zeolites have been widely used in catalysis and adsorption processes because of their suitable zeolite pore structures and exchangeable active sites for selective catalysis and adsorption. The intrapore diffusional phenomena were widely observed in zeolites⁽⁴⁻⁶⁾. Since the magnitude of zeolite pore size is small, generally from 3 Å to 10 Å, the intracrystal diffusion becomes so significant that the diffusion in zeolite channels is much different from molecular diffusion. On the other hand, it is these kinds of small zeolite pore sizes and internal diffusional restrictions that makes certain types of selective catalysis and adsorption successful.

Diffusion in Alumina

Alumina has been widely used as catalyst supports, such as in hydrotreating processes. Several studies have been done on diffusion in alumina or supported alumina catalysts. Nearly all the studies have been carried out with non-adsorbing or weakly adsorbing solutes.

The hydrotreatments of heavy oil, coal-derived liquids, or

some other macromolecular feeds are dependent to a large degree on catalyst intrapore diffusions, because of the comparability of the sizes of reactant molecules to that of catalyst pores. Ho's results⁽⁷⁾ showed that the conversion of coal and the yield of asphaltenes increased as pore diameter increased from 100 to 500 Å, which indicated an alumina intrapore effect on coal hydroliquefaction processes. Kang⁽⁸⁾ observed that coal conversion was controlled by the rate of diffusion of reactants into the internal pores of catalysts. Guin and Curtis⁽⁹⁻¹⁰⁾ also observed increased yields of pentane soluble oils for catalytic coal liquefaction as the sizes of the catalyst particles decreased, which indicated the presence of intrapore diffusional resistances in the catalyst pores. The effect of internal diffusion was much more significant for aged catalysts as indicated by other investigators⁽¹¹⁾.

CLASSIFICATION OF INTRAPORE DIFFUSION

Diffusion in pores may occur by one or more of the three mechanisms: ordinary diffusion, restricted diffusion, and/or surface diffusion. Ordinary diffusion is the molecular diffusion in liquid phase. Restricted diffusion occurs when the size of diffusing molecule is comparable to the size of the pore in which it diffuses. Surface diffusion is the diffusion of adsorbed molecules in the pores of the porous material.

Ordinary Diffusion

Ordinary, or intrapore-volume diffusion, is the predominate mode of diffusion into porous materials. According to ordinary diffusion, the flux of a solute in a porous material is reduced from its value in the bulk solution by simple geometric factors. Thus if the flux of solute "A" in the bulk solution is given by Fick's law

$$N_{Am} = -D_m \nabla C_m \quad (1)$$

where, N_{Am} ---mass transfer flux of solute A based on solution cross-section area, mol A/cm²-s

D_m ---bulk molecular diffusivity, cm²/s

C_m ---bulk concentration of solute A, mol A/cc(bulk)

then, the corresponding ordinary molar flux for the diffusion in porous material is given by

$$N_{Ao} = -\left(\frac{\epsilon}{L} D_m\right) \nabla C \quad (2)$$

where, N_{Ao} ---molar flux of solute A based on the surface of the porous material, mol A/cm²(pellet)-s

C ---concentration of solute A in pore, mol A/cc

ϵ ---porosity of the porous material

L ---tortuosity of pores in the porous material

and the effective diffusivity can be expressed as

$$D_e = \frac{\epsilon}{L} D_m \quad (3)$$

where, D_e ---the effective diffusivity, cm^2/s

The porosity ϵ reduces the flux simply because the fraction $(1-\epsilon)$ of the total area is occupied by the solid and is thus not available for diffusion. The tortuosity L is an empirical attempt to account for several factors including the fact that the actual diffusion path length is lengthened through the porous media by the circuitous route of the pores, as well as the fact that the pores contain constrictions and are of nonuniform diameter.

Restricted Diffusion

When the size of the diffusing molecule is appreciable compared to the pore size of the porous material in which it diffuses, the mass transfer flux can be greatly reduced. The reduced, or restricted diffusion is caused by steric hindrance and viscous drag effects, which will be discussed in detail in the following section.

Surface diffusion

When a diffusing molecule diffuses in a pore, it can adsorb on the wall surface of the pore, and this adsorbed molecule is not necessarily stationary and may diffuse to the other adsorption active sites, or diffuse to return to the liquid phase. Such a flux of diffusion of the adsorbed molecule is referred as surface diffusion⁽¹²⁾. This surface diffusion can be modeled as an additional flux with a surface diffusivity⁽¹³⁾

$$N_{As} = -\rho_p D_s \frac{\partial q_r}{\partial r} \quad (4)$$

where, N_{As} ---surface diffusion flux, mol A/s-cm²(pellet)

q_r ---mol's of solute adsorbed on the pellet at radius r
mol A/g(pellet)

ρ_p ---particle density, g/cc

D_s ---surface diffusivity of adsorbed molecules, cm²/s

The contribution due to the surface diffusion to the total diffusional flux can be substantial, sometimes exceeding the contribution due to the pore-volume diffusion, particularly on the surface of more active adsorption sites, such as zeolites which will be described.

Shape-changeable Molecular Diffusion

Generally, only a molecule with smaller size than that of the pellet pore can diffuse in the pores of a porous material. But some large molecules can diffuse into a pore whose size is smaller than the size of the diffusing molecule. This phenomenon was observed in some porous materials like zeolites⁽¹⁴⁾ and was called shape-changeable molecular diffusion. As shown by Moore⁽¹⁴⁾, molecules having a critical molecular diameter of 9.2 Å can still freely counterdiffuse with cyclohexane in the pore structure of Y zeolite having free pore diameter of 7.4 Å. During this diffusion, the shape, or the kinetic diameter of the molecule, can change to fit the size of the pore. This occurred because the three dimensional array of large cages or cavities with a maximum of about 12 Å

allowed molecules to pass one another, and partially because of the unsaturated attractive forces of the adsorption active sites in the cages.

FACTORS AFFECTING THE INTRAPORE DIFFUSION

As mentioned above, when the size of the diffusing molecule is appreciable compared to the pore size of the porous material in which it diffuses, the mass transfer flux can be greatly reduced. Generally, the reduced, or restricted diffusion has been explained by a combination of two effects⁽¹⁵⁻¹⁶⁾: one is a hindrance effect at the entrance of the pores, the other is a viscous drag from the pore wall of the porous material. Other factors, such as surface adsorption, deactivation of catalysts, can also affect the intrapore diffusion rate.

Hindrance Effect

The hindrance effect was first proposed by Ferry⁽¹⁷⁾ in regard to diffusion in membranes. It was based on the assumption that the diffusing molecules could enter a pore only if they did not strike the wall of the pore, which means that a steric exclusion, or concentration reduction of macromolecules from a portion of volume exists near the wall of the pore, as shown in figure 1. For a spherical molecule entering a circular opening, the partition factor K_p , that is, the effective area for entrance relative to the true area (as shown in figure 1) is:

$$K_p = \frac{A_e}{A_t} \left(1 - \frac{d_m}{d_p}\right)^2 \quad (5)$$

where, A_t ---the total cross-section area of the pore, cm^2

A_e ---the effective area of the opening pore, cm^2

d_m ---the diameter of the diffusing molecule, cm

d_p ---the diameter of the pore, cm

K_p ---the partition factor

Figure 1. Available Volume in Pore

Based on the above discussion, the effective diffusivity in equation (3) can have the following form

$$D_e = \frac{eK_p D_m}{L} \quad (6)$$

Hydrodynamic Drag Effect

When the size of the diffusing molecule approaches the pore size of the porous material, the molecule experiences an increased

frictional drag (hydrodynamic resistance) due to the confinement of the fluid by the pore walls, over and above the drag that would be experienced were the molecule diffusing in an unconfined solvent, as shown in figure 2.

Figure 2. Frictional drag of molecule in pore

The viscous (or hydrodynamic) drag effect was described by the Ladenburg equation⁽¹⁸⁾.

$$K_r = \frac{f_o}{f} = \frac{1}{1 + 2.4 \left(\frac{d_m}{d_p} \right)} \quad (7)$$

where, K_r ---the restriction factor

f ---the frictional force opposing sedimentation

f_o ---the frictional force opposing sedimentation when the diameter of the diffusing molecule is negligible compared to that of the pore

This equation is an empirical equation developed on hydrodynamic grounds to account for viscous drag between settling

particles and the walls of the cylinder in Stokes' Law.

Anderson⁽¹⁹⁾ proposed a slightly different relation to evaluate the viscous drag effect as shown in the following:

$$K_r = 1 - 2.1044 \left(\frac{d_m}{d_p} \right) + 2.089 \left(\frac{d_m}{d_p} \right)^2 - 0.948 \left(\frac{d_m}{d_p} \right)^5 \quad (8)$$

Several other researchers⁽²⁰⁻²²⁾ have derived other correlations for K_r as a function of the ratio of molecular size to the pore size. Actually, the restriction factor K_r is a complex function of solute and pore geometry, flow regime, etc..

Based on the effects of hindrance and hydrodynamic drag, the effective diffusivity in equation (3) can be expressed as

$$D_e = \frac{\epsilon K_r K_p}{L} D_m \quad (9)$$

and the mass transfer flux in a pellet can be expressed as

$$N_A = - \left(\frac{\epsilon K_r K_p}{L} D_m \right) \nabla C_a = - D_e \nabla C_a \quad (10)$$

where, C_a ---available pore concentration,

mol/cc(available porosity)

N_A ---flux based on total pellet area, mol/cm²(pellet area)

Surface adsorption

When molecules diffuse into the pores of porous material, they may adsorb on the surface of the solid. The adsorption of the molecules can decrease the concentration of the solute in the pores of the porous material. There are three types of relationships between the adsorbed amount and the pore fluid concentration of the

solute. One is the linear adsorption isotherm having the following expression

$$q = K_q C_s \quad (11)$$

where, q ---the amount of solute adsorbed on the wall surface of the pores, mol A/g(pellet)

C_s ---the concentration of solute in the available pore volume, mol A/cc(available void)

K_q ---linear adsorption constant, cc/gram

The second is the irreversible adsorption theory which assumes that the amount of adsorption of the solute adsorbed is constant and does not depend on the solute concentration in the liquid phase. The irreversible adsorption can be described as

$$q = q^0 \quad (12)$$

where, q^0 ---saturated amount of solute adsorbed, mol/gram

The third adsorption mechanisms are the non-linear adsorption theories. They are commonly represented by two well known isotherms, namely the Langmuir isotherm and the Freundlich isotherm, as shown in the following, respectively

$$q = \frac{aC}{(1+bC)} \quad (13)$$

$$q = mC^{\frac{1}{n}} \quad (14)$$

where a and b , m and n are all constants.

where a and b, m and n are all constants.

Deactivation of Catalysts

The intrapore diffusion can also be affected by catalyst deactivation. The activity and selectivity of supported porous catalysts could be decreased by the deposition of coke or metals, thus blocking or choking the pores and decreasing the pore diameter of the porous materials during catalytic processes. For example, in H-exchanged mordenite, the effective pore diffusivities decreased about 100 percent because of coke deposits⁽²³⁾. Thai⁽¹¹⁾ found that the effective diffusivities of model compounds for coal liquefaction catalysts decreased greatly for aged catalysts. On the other hand, the diffusivity could be restored, at least in part, after regeneration of the catalyst.

EVALUATION OF THE EFFECTIVE DIFFUSIVITIES

Effective diffusivity is an important parameter, such as in the catalytic reaction when porous materials are used as catalysts or catalyst supports, since the effective diffusivity is related to the mass transfer flux as shown above. Several methods or equations have been used to evaluate the effective diffusivity D_e . Pappenheimer⁽¹⁶⁾ simply combined hindrance in equation (5) and viscous drag term in equation (7) to describe the pore restriction to diffusion, or

$$\frac{D_e}{D_m} = K_p K_r = \frac{(1 - \frac{d_m}{d_p})^2}{(1 + 2.4 \frac{d_m}{d_p})} \quad (15)$$

Renkin⁽²⁴⁾ just combined equations (5) and (8) to give the following equation

$$\frac{D_e}{D_m} = K_p K_r = (1 - \frac{d_m}{d_p})^2 [1 - 2.104 (\frac{d_m}{d_p}) + 2.09 (\frac{d_m}{d_p})^3 - 0.95 (\frac{d_m}{d_p})^5] \quad (16)$$

Some other correlations have also been suggested for calculating the intrapore diffusivities. Conlon⁽²⁵⁾ worked on macromolecules diffusing in micropore membranes and proposed a new correlation

$$\frac{D_e}{D_m} = \exp \left[- \left(\frac{d_m}{d_p} \right) \frac{\delta G}{RT} \right] \quad (17)$$

where, R---gas constant

T---temperature

δG ---the sum of the free energy of interaction between the particles and pores and the free energy of interaction between the particles and solvent

Satterfield⁽²⁰⁾ measured the effective diffusivity organic compounds diffusing in alumina and concluded that the hydrodynamic restricted diffusion model did not work for his results, and obtained the following correlation

$$\log_{10} \left(\frac{D_e}{D_m} \right) = -0.37 - 2.0 \left(\frac{d_m}{d_p} \right) \quad (18)$$

Ma⁽²⁶⁾ argued that when the ratio of molecular size to pore size is large, the relevant dimension on which the effective diffusivity depends is the solute molecular critical diameter, whereas when the ratio of molecular size is close to zero, the relevant dimension is the average diameter, and the relation of the effective diffusivity and the ratio of molecular diameter to pore diameter was suggested as

$$\ln \left(K_p L \frac{D_e}{D_m} \right) = -3.4792 \left(\frac{d_m}{d_p} \right)^3 + 0.836 \quad (19)$$

For the diffusion in zeolites, as mentioned above, diffusion will be accompanied by adsorption and surface diffusion. The adsorbate in gas phase diffuses through the zeolite pores or cages, adsorbs on the adsorption active sites, and the adsorbed molecules will diffuse on the surface of the pore walls⁽⁶⁾. The following equation has been widely used to calculate the effective diffusivity

$$\frac{M_t}{M_\infty} = \frac{2A}{V} \frac{M_o}{M_o - M_\infty} \left(\frac{D_e t}{\pi} \right)^{1/2} \quad (20)$$

where, M_o ---total amount of adsorbate in gas phase at time zero

M_t ---amounts of adsorbate adsorbed at time t

M_∞ ---amounts of adsorbate adsorbed at equilibrium

V ---volume of zeolite

A ---external surface area of zeolite

As stated above, intrapore effective diffusivities can be evaluated by several methods, according to the diffusing systems used. The effective diffusivity can also be evaluated by data fitting with mathematical models, as discussed below.

MATHEMATICAL INTRAPORE DIFFUSIONAL MODEL

As mentioned above, knowing the diffusional mechanisms in porous materials is very important both in theoretical research and in industrialization. But due to the complexity of molecules diffusing into the porous materials, it is difficult to determine the diffusivities of the reactant and product molecules. Generally, the constant-volume technique with appropriate model compounds can be utilized to determine diffusivities by measuring the rate of accumulation or depletion of solute in the bulk fluid, and then fitting the experimental data with mathematical models.

Several mathematical models have been developed to describe the diffusion mechanisms in internal particle pores^(3,11,22,27-30). Although the main idea was the same, the resulting mathematical models were slightly different based on different assumptions. The following mathematical model has been used by several researchers.

Consider a particle pellet immersed in a finite bath containing solute "A" and solvent "B", the solute molecules "A" are diffusing into the porous particle pellet. The following general assumptions will be used in this model:

1. Chemical reaction is not considered in this process;

2. The particle pellet and the diffusing molecules are assumed as perfect spheres;
3. Surface diffusion is neglected;
4. The solute is assumed to have both Brownian and hydrodynamic characteristics, the sizes of the diffusing molecules are larger than the sizes of solvent molecules, and the solvent is a continuum;
5. There are no particle-particle interactions;
6. Also, it is assumed that the stirring speed of the solution is so high that the concentration in the bath is dependent only on time, not on position, and the external mass transfer can be neglected.

Based on the above assumptions, the following mathematical diffusional model can be derived.

DIFFUSIONAL FLUX

Diffusional Flux in Single Pore

According to Fick's law, the mass transfer flux in a single pore can be expressed as

$$N_{Aa} = -D_m \nabla C_a \quad (21)$$

where, N_{Aa} --- mass transfer flux of solute A based on available pore cross-section area, mol A/cm²(available pore area)-s

D_m --- bulk molecular diffusivity, cm²/s

C_a --- available pore concentration of solute A,
mol A/cc(available porosity)

Since a portion of the total pore volume near the pore wall is

not accessible to the diffusing molecules, the relation between the available pore concentration and the total pore concentration is:

$$K_p = \frac{C_p}{C_a} = \frac{\text{available pore area, cm}^2}{\text{total pore area, cm}^2} \quad (22)$$

where, K_p ---the partition factor

C_p ---total pore concentration, mol A/cc(total porosity)

and K_p can be calculated by equation (5). Then the total pore flux is:

$$N_{Ap} = K_p N_{Aa} = -K_p D_m \nabla C_a \quad (23)$$

Also, by considering the restricted factor K_r , which can be calculated by equation (8), then, the mass transfer flux in single pore can be expressed based on the total pore area as:

$$N_{Ap} = K_p K_r N_{Aa} = -K_p K_r D_m \nabla C_a \quad (24)$$

or

$$N_{Ap} = -K_r D_m \nabla C_p \quad (25)$$

where, N_{Ap} ---flux based on the total pore area,
mol A/cm²(total pore area)-s

Diffusional Flux in Pellet

For the flux N_A based on the total pellet area, two factors will be used; one is the porosity ϵ ,

$$\epsilon = \frac{\text{pore area, cm}^2}{\text{pellet area, cm}^2} = \frac{\text{pore volume, cm}^3}{\text{total pellet volume, cm}^3} \quad (26)$$

The other is the tortuosity L . Then, the pellet flux is:

$$N_A = \frac{e}{L} N_{Ap} = -\frac{eK_p K_r}{L} D_m \nabla C_A = -D_{ep} \nabla C_A \quad (27)$$

where

$$D_{ep} = \frac{eK_p K_r}{L} D_m \quad (28)$$

or

$$N_A = \frac{e}{L} N_{Ap} = \frac{eK_r}{L} D_m \nabla C_p = D_{ep} \nabla C_p \quad (29)$$

where,

$$D_{ep} = \frac{eK_r}{L} D_m \quad (30)$$

where, N_A ---flux based on total pellet area, mol A/cm²(pellet)-s

DIFFUSIONAL MODEL

Mass Balance in porous Particle Pellet

Take a shell material balance in a spherical pellet

$$[N_A 4\pi r^2]_r - [N_A 4\pi r^2]_{r+\Delta r} = \frac{\partial}{\partial t} [C_p e 4\pi r^2 \Delta r + q_p 4\pi r^2 \Delta r] \quad (31)$$

or

$$e \frac{\partial C_p}{\partial t} + \rho_p \frac{\partial q}{\partial t} = -\frac{1}{r^2} \frac{\partial}{\partial r} [r^2 N_A] \quad (32)$$

where, q ---mol's adsorbed per gram of pellet, mol A/g(pellet)

r ---radius of the pellet sphere, cm

ρ_p ---bulk pellet density, g/cc(total pellet volume)

t ---immersing time, s

For a linear adsorption isotherm, the adsorption term q is

given by equation(11). Also, for the pellet mass transfer flux N_A , using equation (26), for the total pore concentration C_p , using equations (22), then equation (32) can be changed as follows:

$$(K_p e + \rho_p K_q) \frac{\partial C_a}{\partial t} = \frac{D_e}{r^2} \frac{\partial}{\partial r} (r^2 \frac{\partial C_a}{\partial r}) \quad (33)$$

and

Boundary conditions:

$$r=0, \frac{\partial C_a}{\partial r} = 0 \quad (34)$$

$$r=R, C_a = C_b(t) \quad (35)$$

Initial condition:

$$t=0, C_a = 0 \quad (36)$$

where, $C_b(t)$ ---bath concentration at time t , mol/cc(fluid)

Equation (34) states that the concentration distribution in the spherical particle is symmetric, and equation (35) assumes that no external diffusion resistance exists around the particle.

If one uses the total pore concentration C_p , then equations (33-36) will have the following form:

$$(K_p e + \rho_p K_q) \frac{\partial C_p}{\partial t} = \frac{D_e}{r^2} \frac{\partial}{\partial r} (r^2 \frac{\partial C_p}{\partial r}) \quad (37)$$

and

Boundary conditions:

$$r=0, \frac{\partial C_p}{\partial r}=0 \quad (38)$$

$$r=R, C_p=K_p C_b(t) \quad (39)$$

Initial condition:

$$t=0, C_p=0 \quad (40)$$

Mass Balance in the Bath

The mass balance for solute "A" in the bath is as follows:

$$\frac{d(V_b C_b)}{dt} = 4\pi R^2 n N_A |_{r=R} = -4\pi R^2 n D_e \left(\frac{\partial C_a}{\partial r} \right) |_{r=R} \quad (41)$$

Initial condition:

$$t=0, C_b=C_{b0} \quad (42)$$

where, C_{b0} ---initial bath concentration at $t = 0$, mol/cc(fluid)

n ---the number of the particle pellets

V_b ---bath fluid volume, cc

Using the total concentration C_p , equation (41) can be expressed as:

$$\frac{d(V_b C_b)}{dt} = 4\pi R^2 n N_A |_{r=R} = -4\pi R^2 n \frac{D_e}{K_p} \left(\frac{\partial C_p}{\partial r} \right) |_{r=R} \quad (43)$$

Dimensionless Form of the Model

In equations (33-36) and equations (41-42), let:

$$\xi = \frac{r}{R} \quad (\text{dimensionless radius}) \quad (44)$$

$$\theta_b = \frac{C_b}{C_{bo}} \quad (\text{dimensionless bath concentration}) \quad (45)$$

$$\theta_a = \frac{C_a}{C_{bo}} \quad (\text{dimensionless available pore concentration}) \quad (46)$$

$$\tau = \frac{t}{R^2} \frac{De}{K_p e + \rho_p K_q} \quad (\text{dimensionless time}) \quad (47)$$

$$B = \frac{V_b}{\frac{4}{3} n \pi R^3} \frac{1}{K_p e + \rho_p K_q} = \frac{V_b}{V_p} \frac{1}{K_p e + \rho_p K_q} \quad (48)$$

where, V_p --- total particle volume, cc

then, equations (33-36) and equations (41-42) can be changed as:

$$\frac{\partial \theta_a}{\partial \tau} = \frac{1}{\xi^2} \frac{\partial}{\partial \xi} \left(\xi^2 \frac{\partial \theta_a}{\partial \xi} \right) \quad (49)$$

$$\frac{\partial \theta_a}{\partial \xi} \Big|_{\xi=0} = 0 \quad (50)$$

$$\theta_a \Big|_{\tau=0} = \theta_b(\tau) \quad (51)$$

$$\theta_a \Big|_{\tau=0} = 0 \quad (52)$$

and

$$\frac{d\theta_b}{d\tau} = -\frac{3}{B} \frac{\partial \theta_a}{\partial \xi} \Big|_{\xi=1} \quad (53)$$

$$\theta_b \Big|_{\tau=0} = 1 \quad (54)$$

The above PDEs and ODEs can be solved analytically (see Bird⁽³¹⁾), and the solution is:

$$\theta_b = \frac{B}{1+B} + 6B \sum_{k=1}^{\infty} \frac{\exp(-b_k^2 \tau)}{B^2 b_k^2 + 9(1+B)} \quad (55)$$

where, the b_k are the non-zero roots of

$$\tan(b_k) = \frac{3b_k}{3+Bb_k^2} \quad (56)$$

DATA FITTING OF THE MODEL

As shown in equation (55), if surface adsorption is treated as linear, the solution can be obtained analytically. From this equation, the constant B can be obtained from the infinite dimensionless concentration, that is, at infinite time, equation (55) becomes

$$\theta_b = \frac{B}{1+B} \quad (57)$$

Also, by data fitting, the effective diffusivity D_e can be obtained.

In order to check the model described above, experimental data were chosen from ref(3) for the diffusion of model compounds

in alumina. Naphthalene, coronene, octa-ethylporphyrin and tetraphenylporphyrin were used as diffusing model compounds respectively, cyclohexane was used as solvent. Table 1 lists parameters used in the above equation for alumina and these model compounds. Figures 1-4 plots the experimental data from ref.(3). From these figures, the diffusivities and adsorption constants can be obtained by data fitting, and the fitted results are shown in table 2. Also, the diffusivities can be calculated from equation (28), in which K_p and K_r were calculated from equation(5) and equation (8), respectively, as shown in the following equation

$$D_o = \frac{\epsilon}{L} D_m \left(1 - \frac{d_m}{d_p}\right)^2 \left[1 - 2.1044 \left(\frac{d_m}{d_p}\right) + 2.089 \left(\frac{d_m}{d_p}\right)^2 - 0.948 \left(\frac{d_m}{d_p}\right)^3\right] \quad (58)$$

The results of calculated diffusivities are also shown in table 2.

From table 2, it can be seen that diffusivities obtained from data fitting of the model are very close to those calculated from equation (58).

Table 1 Parameters of alumina and model compounds

alumina	$\rho_p, \text{g/cc}$	$d_p, \text{\AA}$	ϵ	L
	1.21	98	0.73	1.5
bath	V_p	400 cc		
model compound	$d_m, \text{\AA}$	$D_m, \times 10^6 \text{cm/s}$	R, cm	V_p, cc
naphthalene	6.9	11.2	0.101	1.747
coronene	11.1	7.45	0.0281	0.379
octa-ethylporphrin	15.3	4.36	0.0157	0.0983
tetra-phenylporphrin	19	4.37	0.0157	0.121

Table 2. Fitted D_e 's and K_q 's from exp^t data by math model

	$K_q, \text{cc/g}$	$D_e, \times 10^6 \text{cm}^2/\text{s}$	$D_e^*, \times 10^6 \text{cm}^2/\text{s}$
naphthalene	47	3.9	4.02
coronene	726	2.5	2.18
octa-ethylporphrin	3363	1.02	1.03
tetra-phenylporphrin	2134	0.99	0.84

note * : calculated from equation(58)

DISCUSSION

As discussed above, intrapore diffusion is a very complex problem related to several types of diffusion, such as restricted diffusion, surface adsorption and surface diffusion. The intrapore diffusion rate will be restricted significantly when the size of the diffusing molecule is appreciable compared to the size of the pore. Many factors influence the intrapore diffusion, for example, the steric hindrance caused by the unaccessible portion of the pore volume, the increased drag caused by the frictional drag between the diffusing molecules and the pore walls, and the blocking of the pores caused by coke or metal depositions during the catalyst deactivation.

Several models have been developed by investigators to describe the mechanisms of internal diffusion in porous catalysts, most of them were based on mass transfer theories. The influences of intrapore diffusion on effective diffusivities can be evaluated either by theoretical equations, or by fitting experimental data of intrapore diffusion mathematical models.

REFERENCES

1. Fuchs, E., et al., Biochem. Biophys. Res. Commun., 5, 196(1961)
2. Pappenheimer, J. R., Physiol. Rev., 33, 387(1953)
3. Chantong, A., Ph.D Degree Dissertation, University of Utah, 1982
4. Barrer, R. M., et al., Trans. Faraday Soc., 44, 195(1953)
5. Barrer, R. M., et al., Trans. Faraday Soc., 49, 1049(1953)
6. Barrer, R. M., Adv. Chem. Series, 102, 1(1971)
7. Ho, P. N., and Weller, S. W., Fuel Processing Tech., 4, 21
(1979)
8. Kang, C. C., "Proceedings of International Conference on Coal
Science," Pittsburgh, 75, 1983
9. Guin, J. A., Curtis, C. W., et al., Fuel Processing Technol.,
7, 277(1983)
10. Guin, J. A., Curtis, C. W., et al., Paper presented at the
Spring National AIChE Meeting, Atlanta(1984)
11. Tsai, K. J., Ph.D Degree Dissertaion, Auburn University, 1985
12. Komiyama, H., et al., AIChE J., 20, 1110(1974)
13. Bischoff, K. B., et al., "Chemical Reactor Analysis and
Design," John Wiley (1979)
14. Moore, R. M., et al., AIChE J., 18, 816(1972)
15. Deen, W. M., AIChE J., 33(9), 1409(1987)
16. Pappenheimer, J. R., Physiol. Rev., 33, 387(1953)
17. Feery, J. D., J. Gen. Physiol., 20, 95(1936)
18. Solomon, A. K., J. Gen. Physiol., 51, 335S(1968)
19. Anderson, J. L., et al., Biophysical J., 14, 130(1974)
20. Satterfield, C. N., et al., AIChE J., 19, 628(1973)

21. Coulton, C. K., et al., AICHE J., 21, 289(1975)
22. Rhee, Y. W., Ph.D Degree Dissertation, Auburn University, 1989
23. Butt, J. B., et al., J. Catal., 37, 158(1975)
24. Renkin, E. M., J. Gen. Physiol., 38, 225(1954)
25. Conlon, T. et al., Aust. J. Chem., 25, 695(1972)
26. Ma, Y. H., et al., J. AICHE, 23, 303(1977)
27. Wei, J., AICHE J., 36(2), 242(1990)
28. van Vuuren, D. S., et al., AICHE J., 30(4), 593(1984)
29. Do, D. D., et al., AICHE J., 32(7), 1088(1986)
30. Lenhoff, A. M., J. Chromatography, 384, 285(1987)
31. Bird, R. B., Transport Phenomena, p357-360, 1960

END

**DATE
FILMED**

10 / 14 / 92