*Aspects of Photoionization of Impurities
and Electron Transfer in Ionic Crystals*

Final Report to Department of Energy
Office of Basic Energy Sciences
Contract Number De-FG02-84ER45146

DOE/ER/45146--7

DE93 008544

Donald S. McClure
Department of Chemistry
Princeton University
Princeton, New Jersey 08544
February 10, 1993

Two lines of research were supported by the DoE grant from September 1984 through September 1991. The principal one was the study of photoionization of impurity ions in ionic crystals and the trapping of the released electrons. Support for the photoionization study was provided by the development of two-photon spectroscopy of impurity ions in crystals, and this method was further extended to several key examples.

A. Research Programs

1. Photoionization of Impurity Ions in Host Crystals.

The divalent rare earth ions may be photoionized with visible or near UV light leaving the ion in its more normal trivalent state. The first work reported under this contract incorporated a review of the ionization energies of these ions in CaF_2 , SrF_2 and BaF_2 , and also gave some new photoconductivity data. These data were compared to a theory based on an electrostatic model, and it was shown to be successful in predicting the ionization energy of this series.^{1,2}

These results have been used by others to predict photoionization in laser materials, where it would reduce their efficiency.^(a)

We believed we had identified spectroscopic evidence for photoionization in the spectra of Eu^{2+} and Sm^{2+} in BaF_2 : the evidence was the broadening of the spectra compared to the $f \rightarrow d$ spectra of those same ions in SrF_2 . Later we sought

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

further evidence in the broadening of the $f \rightarrow f$ two-photon spectra of these ions.⁵ It was important to have both spectroscopic and photoconductivity data to prove photoionization since each method has some drawbacks. A paper about to be published illustrates some of the complexities of this field.⁶

Another aspect of this work is the determination of where the electrons go after being photoejected from the impurity site. Fuller in ref. 5 used SrF_2 doubly doped with Eu^{2+} and Sm^{3+} . In this example we expected the electrons ejected from Eu^{2+} to be trapped by Sm^{3+} . Fuller measured the yield of ejected and trapped electrons and found the absolute efficiency at several wavelengths. He also discovered a remarkable temperature dependence of the electron yield. It was 10 percent efficient at 218 nm and 300 K, but only about 0.01 percent efficient at 200 K. From 200 to 300 K the yield could be fitted to an activation formula with a heat of activation of 3000 cm^{-1} ($\sim 0.37 \text{ eV}$). This value was interpreted as the energy needed to eject an interstitial fluoride ion charge compensator from the vicinity of the Sm^{3+} ion acting as a trap. Most of the Sm^{3+} ions have a F^- in the nearest neighbor interstitial site at $(\frac{1}{2} 00)$. Since the photocurrent did not show such a temperature dependence we speculated that it was due only to the uncompensated trapping sites. (The photocurrent in an insulator with blocking electrodes is determined by the projection in the field direction of the path length of electrons from donor ion to trap: the uncompensated Sm^{3+} are not numerous but have a large trapping cross section, so each electron ending its trajectory in such a trap contributes a large amount to the current.) Trapping at uncompensated sites would not require the ejection of a fluoride ion and therefore there would be no activation energy and no temperature dependence. Since there are so few uncompensated Sm^{3+} , they would make only a small contribution to the yield.

This explanation of the temperature dependence of the yield, and temperature independence of the photocurrent was applied to $\text{BaF}_2:\text{Eu}^{2+}:\text{Sm}^{3+}$ in ref. 6. Here it was found that upon illumination, electrons released from Eu^{2+} were exclusively trapped by uncompensated Sm^{3+} until these traps were completely filled. With further illumination the compensated Sm^{3+} acted as traps. In this lattice, however, it is not necessary for the Sm^{3+} to release its F^- compensator as this ion is in a more distant interstitial site, ($\frac{1}{2}, \frac{1}{2}, \frac{1}{2}$), and the $\text{Sm}^{3+}-\text{F}^-$ pair remains a fairly good trap. In addition it was observed that there is almost no temperature dependence of this trapping process.

In ref. 6 it was further observed that the trapped electrons at $\text{Sm}^{2+}-\text{F}^-$ sites could be photoionized with about 0.5 eV less energy than from the Sm^{2+} sites having no nearby F^- ions. Clearly the presence of the F^- ion near a Sm^{2+} will make it easier to detrap the electron, and this experiment made a quantitative measurement of its effect.

The technique of using Eu^{2+} as a source of electrons is especially useful in making comparative measurements of electron trapping. Electrons are released uniformly in the crystal and traps of all kinds get filled at rates proportional to their cross sections. We are continuing this work to find relative trapping cross sections by measuring the filling rates.

The $\text{BaF}_2:\text{Eu}^{2+}:\text{Sm}^{3+}$ crystal contained an accidental impurity of Ce^{3+} . This gave us the opportunity to find the cross section for $\text{Ce}^{3+}-\text{F}_i^-$ relative to $\text{Sm}^{3+}-\text{F}_i^-$. It was found that $\text{Ce}^{3+}-\text{F}_i^-$ is a much poorer trap. This presumably has to do with the different electron configurations in the filled ground states, f^5 for Sm^{2+} and fd for Ce^{2+} . This result provides an important clue for the development of a theory of trapping.

In closely related research we studied the photochemistry which can occur in $\text{CaF}_2:\text{Ce}^{3+}$.⁷ Our work followed publications by Hamilton and coworkers which

showed that Ce^{3+} is converted to Ce^{2+} in a two-photon process.^b No mention was made of Ce^{4+} . We added temperature as a variable and also used Na^+ doped $\text{CaF}_2:\text{Ce}^{3+}$ where Na^+ acts as a charge compensator. It was found that although irradiation of $\text{CaF}_2:\text{Ce}^{3+}$ at 308 nm (with an excimer laser) produced Ce^{2+} at room temperature, at 77 K the only change was that the charge compensating F_i^- moved from the $00\frac{1}{2}$ to the $\frac{1}{2}\frac{1}{2}\frac{1}{2}$ site. Annealing the crystal at 300 K restored the compensator to its more stable $00\frac{1}{2}$ site. When Na^+ was the compensator, we observed the production of Ce^{+2} at 77 K. At 300 K, however, Ce^{+2} is observed to appear briefly and then to be replaced by Ce^{+3} and defects which cause a blue color. Diffusion processes are responsible for this change since irradiation for a few seconds followed by minutes in the dark results in the blue color. A plausible mechanism was developed to account for all of the observations; it involves excitation of the interstitial fluoride, or the action of F^- vacancies created by Na^+ doping.

These studies of the rare earths in fluorite structure crystals are based on a large amount of previous work.^c A review up to 1974 appears in the book edited by Hayes.^d Our work has added: (1) more understanding of the nature of photoconductivity in these crystals, (2) more quantitative values for photoionization yields, (3) better understanding of trapping processes, (4) new ideas on photochemical mechanisms.

Since charge compensators are so important for impurity ions in crystals, we decided to devote some time to the very interesting case of Ce^{3+} in CaF_2 or SrF_2 with Na^+ charge compensators.⁸ We already had the spectrum due to the $f \rightarrow d$ transition in the near UV and it showed some 20 lines due to the zero phonon transitions of Ce-Na pairs with varying Ce-Na distances. We could identify several of these pairs and their distances. We made a stupid mistake in identifying what appeared to be a case of spectral hole burning which, on later

investigation, turned out to be an experimental artifact.^{8a} Most of the publication is correct, however, and another publication on the laser-induced fluorescence is due in the near future.¹²

Our next work in this area is to use Cu^+ as the charge compensator and to try to observe electron transfer from Cu^+ to Ce^{3+} . This system would provide a series of known donor-acceptor distances for electron transfer.

2. Two-Photon Spectroscopy of Impurity Ions in Host Crystals.

In a centrosymmetric system, such as Sm^{2+} in SrF_2 or Ni^{2+} in MgO , the $f \rightarrow f$ and $d \rightarrow d$ transitions are forbidden as one-photon electric dipole processes. One-photon magnetic dipole processes are effected by a T_{1g} operator. Thus, the zero-phonon lines of many transitions in the rare earth or transition metal series cannot be observed except for the special case noted above. We had used this method for $\text{NaF}:\text{Cu}^+$ and had been very successful in unraveling the spectrum of this important example of an impurity ion in a crystal. Therefore, we wanted to extend our work to several other examples whose spectra needed to be clarified.

The first case was Mn^{4+} in Cs_2GeF_6 .⁹ The spectral assignments had been attempted by Helmholtz and his students but some questions remained which we could answer.⁹ We needed tunable infrared photons in the region of 1.2μ and started a collaboration with Paul Rabinowitz at Exxon who had worked out the theory and practice of the stimulated Raman effect. A visible dye laser is focussed into a cell containing hydrogen gas at a moderate pressured (200 psi): with multiple passes, good power levels in the first, second and third Stokes shifts are obtained giving tunable outputs in the required spectral regions. The results of this work were remarkable for the time and cleared up the problems with the spectral assignments.⁹ A short review of the methods we developed and some results was written.¹⁰

The next major example was MgO:Ni^{2+} , a simple system, but it was not completely understood.^f Many zero phonon lines had not been identified. For this we needed a highly sensitive infrared detector since the fluorescence occurs at 7900 cm^{-1} , as well as tunable IR at 2.5μ . This work was again done at Exxon. The results of this work gave us the zero phonon lines of six electronic states and clarified the vibrational structure of the spectral transitions.¹¹

Fuller used two-photon spectroscopy in his work to find spectroscopic evidence for autoionization.^{3,4,5} For example, it was necessary to examine the line widths of $f \rightarrow f$ transitions in energy regions where they are covered over by $f \rightarrow d$ transitions. The latter are strong in one photon spectra but absent from two-photon spectra, whereas, the $f \rightarrow f$ transitions are strong in two-photon spectra. This method was quite successful in revealing the "hidden" $f \rightarrow f$ transitions.

Two-photon spectroscopy studies have continued in this laboratory with other funding. It is the best way to clear up problems in spectral identification in symmetrical systems and we will continue to work on important examples.

Publications credited to DoE 1985-1991.

1. Excitons Trapped at Impurity Centers in Highly Ionic Crystals. D. S. McClure and C. Pedrini, *Phys. Rev. B*, 32, 8465, (1985).
2. Photoionization Threshold of Rare Earth Impurity Ions in $\text{Eu}^{2+}:\text{CaF}_2$, $\text{Ce}^{3+}:\text{YAG}$ and $\text{Sm}^{2+}:\text{CaF}_2$. C. Pedrini, F. Rogemond and D. S. McClure, *J. Appl. Phys.*, 59, 1196 (1986).
3. Measurement of Ionization Rate of Photoexcited Divalent Rare Earth Ions in Fluorite-type Crystals. Robert Fuller and Donald S. McClure, *J. Luminescence*, 38, 193 (1987).
4. Determination of Photoionization Rates of Divalent Samarium Doped in Alkaline Earth Fluorides. Robert L. Fuller and Donald S. McClure, *J. of Luminescence* 45, 354-6 (1990).
5. Photoionization Yields in the Doubly Doped $\text{SrF}_2\text{Eu:Sm}$ System. Robert L. Fuller and Donald S. McClure, *Phys. Rev.* 43, 27 (1991).
6. Photoionization and Trapping of Electrons in the System $\text{BaF}_2\text{Eu:Sm}$. Wanfeng Mou and Donald S. McClure, *Phys. Rev. B*, (1993) in press.
7. Photoionization and Photochemical Production of Color Centers in Ce^{3+} and $\text{Ce}^{3+}:\text{Na}^+$ Doped CaF_2 . G.S. Hollingsworth and D.S. McClure, *Phys. Rev. B* (1993) submitted.
8. $\text{Ce}^{3+}:\text{Na}^+$ Pairs in CaF_2 and in SrF_2 : Absorption and Laser-excitation Spectroscopy, and the Observation of Hole Burning. Dee William Pack, William J. Manthey and Donald S. McClure, *Phys. Rev. B*, 40, 9930-9944 (1989).
- 8a. Erratum *ibid.* *Phys. Rev. B* 44, 3494 (1991).
9. Two-Photon Electronic Spectroscopy of $\text{Cs}_2\text{GeF}_6:\text{Mn}^{4+}$. R.-L. Chien, J. Berg, D.S. McClure, P. Rabinowitz and B. N. Perry, *J. Chem. Phys.* 84, 4168 (1986).
10. Techniques and Applications of Two-photon Spectroscopy of Inorganic Solids. D.S. McClure, Standard Publication 1066 (American Society for Testing and Materials) (1990) p. 21-35.
11. Two-Photon Spectroscopy of $\text{MgO}:\text{Ni}^{2+}$. Cecelia Campochario, Donald S. McClure, Paul Rabinowitz and Shawn Dougal, *Phys. Rev. B*, 43, 14 (1991).
12. $\text{Ce}^{3+}:\text{Na}^+$ Pairs in CaF_2 and SrF_2 : selective excitation and emission spectra of individual species. D.W. Pack and D.S. McClure, in preparation.

Other references

- a. Excited State Absorption Measurements of Sm^{2+} in CaF_2 , SrF_2 and SrCl_2 .
J.K. Lawson, H.W.H. Lee, S.A. Payne and L.A. Boatner, OSA Proceedings on Advanced Solid State Lasers, 1991, Vol. 10, p. 386.
Also, Lawson and Payne, Excited State Absorption of Eu^{2+} -doped Materials, *Phys. Rev.*, in press. 1993.
- b. G.S. Pogatshnik and D.S. Hamilton, *Phys. Rev.* B36, 8251 (19857).
- c. J.L. Merz and P.S. Pershan, Charge Conversion of Irradiated Rare Earth Ions in Calcium Fluoride, *Phys. Rev.* 162, 217, 235 (1967).
D.L. Staebler and S.E. Schnatterly, Optical Studies of a Photochromic Color Center in Rare-Earth-Doped CaF_2 . *Phys. Rev.*, B3, 516 (1971).
Also related: *Phys. Rev.* B3, 527, 536 (1971).
- d. W. Hayes, Crystals with the Fluorite Structure, Oxford, 1974.
- e. L. Helmholtz and M.E. Russo, *J. Chem. Phys.* 59, 5455 (1973).
- f. B.D. Bird, G.A. Osborne and P.J. Stephens, *Phys. Rev.* B5, 1800 (1972).

B. Personnel

The grant from DoE supported several people during their graduate years and helped toward their Ph.D. theses.

Cecelia Campochiaro - Ph.D. thesis: Two-Photon Spectroscopy
Now at Stanford University as a postdoctoral fellow.

Robert Fuller - Ph.D. thesis: Photoionization
Postdoctoral work at Rutgers, now at Colgate.

Dr. Gary Hollingsworth, postdoctoral fellow from UCLA., Photochemistry,
Two-Photon Spectroscopy.

Dee Pack - Ph.D. thesis: $\text{CaF}_2\text{:Ce:Na}$
Postdoctoral work at Stanford, now at Aerospace Corp.

Mr. Wanfeng Mou - Ph.D. expected late 1993. Trapping in Fluorite Crystals.

John Berg - Ph.D. thesis, Two-Photon Spectroscopy. Postdoctoral at MIT.
Now at Los Alamos National Laboratory.

Ring-ling Chien - Postdoctoral from University of Chicago. Two-Photon
Spectroscopy. Now at Varian Assoc., Palo Alto, CA.

C. Concluding remarks:

The principal investigator expresses his appreciation for the support of Basic Energy Sciences of DoE. During the period of seven years of this support, seven people received advanced training in scientific research and have become valuable creative scientists. The research areas supported by the grant have attracted the attention of other scientists around the world and have inspired further research in these areas. The principal investigator receives invitations to speak at international meetings and university seminars on these subjects.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

DATE
FILMED

3 / 23 / 93