DOE/PC/91290-74

2

TECHNICAL PROGRESS REPORT #5

Title: Non-Intrusive Measurement of Particle Charge: Electrostatic Dry Coal Cleaning
(DE-FG22-91PC91290)

Organization: Center for Applied Energy Research

DOE/PC/91290--T4

University of Kentucky

DE93 006485

3572 Iron Works Pike

Lexington, KY 40511

Report Period: 7/1/92 - 9/30/92

Grant Period: 8/29/91 - 8/28/94

1. Grant Objective: No change
2. Technical Approach Changes: No changes. The project is approximately three months behind the schedule displayed in the original proposal. However, it is anticipated that this deficiency will be eliminated during the next quarter.
3. Progress Report by Task:

Task 1. Sample Acquisition and Preparation

All coal and mineral samples have been obtained and prepared for the PDPA experiments. The most recent acquisitions included mineral pyrite, illite, montmorillinite, and alumina. Preparation of these samples was successfully completed; however, it was determined by scanning electron microscopy (SEM) analysis that difficulty in sieving illite and kaolinite to a size of -200/+325 mesh was a result of excessive grinding which produced particle sizes in the range of 5-10 micrometers. At such a size, the powders tended to "stick" to the vibratory feeder in the experimental apparatus, thereby eliminating the possibility of uniform feed rates to

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

182

the electrostatic separator. These minerals will be reordered and subjected to alternate grinding that does not produce such fine particle sizes.

Task 2: PDPA - Charge Measurement

Summary of Work

Triboelectric charging/electrostatic separation experiments were performed using silica, alumina and glassy carbon samples. The average charge on silica and alumina particles was a near-linear function of their velocity in the Cu tribocharge loop, with their charge distribution becoming wider at higher velocities. The average charge of glassy carbon particles was near zero; this charge distribution caused particles to deposit on both positive and negative electrodes.

An improved theory for particle charging and electrostatic separation was developed. It includes the use of probability functions and is briefly described below.

Theoretical Basis

The behavior of a single, spherically shaped, charged particle in a flow stream is determined by the sum of forces acting upon it. For our experiments, we define a coordinate system with $\underline{x}$ pointing in the direction of the electric field and $\underline{y}$ in the direction of gas flow (downwards). In the $\underline{x}$ direction the forces include drag and the electric field force, where the electrical force is given by:

$$F_e = qE, \quad (1)$$

where q is the charge on the particle and E is the electric field strength.

Under laminar flow conditions (as in our experiments), the drag force is caused by the difference between the velocities of the particle and the gas. When the Reynolds number is small, the drag force can be calculated by:

$$F_D = \frac{C_D \pi \rho D^2 V^2}{8} \quad (2)$$

using the following relationships:

$$C_D = \frac{24}{R_e} \text{ and } R_e = \frac{\rho D V}{\mu},$$

where V is the velocity in the x direction and D is the particle diameter.

Therefore, the governing differential equation for the particle motion in x-direction can be written as:

$$m \frac{dV}{dt} = F_E - F_D = qE - 3\pi D\mu V \quad (3)$$

where m is the mass of the particle.

The equation can be rewritten in terms of the particle diameter and density.

$$\frac{dV}{dt} + \frac{18\mu}{D^2 \rho_p} V - \frac{6qE}{\pi D^3 \rho_p} = 0 \quad (4)$$

where ρ_p is the density of the particle.

The initial condition is: at $t = 0$, $V = 0$. An analytical solution is obtained in which the expression for the charge, q, is given as:

$$q = \frac{3\pi D\mu V}{E} \frac{1}{1 - e^{\frac{-18\mu t}{\rho_p D^2}}} \quad (5)$$

Further integration yields a trajectory equation of the particle:

$$x = x_o + \frac{qE}{3\pi D\mu} \left[t + \left(e^{\frac{-18\mu t}{\rho_p D^2}} - 1 \right) \frac{\rho_p D^2}{18\mu} \right], \quad (6)$$

where x_o is the initial position where the particle enters the chamber.

The particle travel time, t , in those equations is decided by the y -direction equation. If it is assumed that the particle velocity is linearly decelerating, the time of travel to any point y can be expressed as:

$$t = 2y/(U_0 + U); \quad (7)$$

where U_0 is the particle vertical velocity at $t = 0$ and U is the vertical velocity at point y .

Equation 6 and 7 determine the behavior of a particle having known density, diameter, and initial position and velocity.

The assumptions used in establishing equations 6 and 7 would lead to minimal (but acceptable) error, which primarily results from using the Stokes flow assumption. The time of travel to any point in the electrostatic separator can be obtained by using the measured vertical velocity along the approximate trajectory of the particle.

The average particle diameter for the silica spheres was determined by PDPA and SEM measurements to be 60 micrometers. These measurements also showed that there was a distribution of sizes that approximated to a high degree a normal or Gaussian distribution. Hence, silica particles fed to the tribocharger and the electrostatic separator had a Gaussian size distribution and it is assumed that the non-idealized minerals (i.e. not having spherical shape) will also have a Gaussian size distribution. This assumption impacts particle velocities and their subsequent positions within the electric field such that it can be assumed that the initial velocity, U_0 , and position, x_0 , at $t=0$ follow a normal distribution.

The behavior of the particles after $t=0$ and $x=0$ can be predicted by the probability density distributions for D , U_0 and x_0 in conjunction with equations 6 and 7.

A computer program was developed to incorporate the equations with a normal distribution. This program included the use of a mathematical subroutine from the main frame computer at the University of Kentucky. However, no particle-particle interactions were incorporated into the model because the experiments were (and will be) performed under conditions in which the volume fraction of the particles in the gas are small. Using the program it is also possible to analyze sensitivity functions, ie. which factors play an important role or control particle trajectories in the separator for each sample and condition under investigation. In our experiments it was determined that the charge, q , was the main parameter affecting the measured particle number density along the x direction in the separator. Hence, the difference in particle charge is the major reason for the distribution of particles in the separation chamber.

Results

Charge magnitude and distribution data for silica and alumina particles from our experimental equipment are displayed in Figures 1-3. Figure 1 shows the charge distribution for 50-70 micrometer spherical silica when the velocity in the tribocharger was 3.3 m/s and the electric field intensity was 100 KV/m. Also included in this plot is the Gaussian distribution fit to the data. The average charge (Coulombs - C) obtained for the silica under these conditions was 6.2×10^{-14} C ($\sigma = \pm 4.3 \times 10^{-14}$).

As shown in Figure 2, the average charge and the charge distribution are a function of the particle velocity in the tribocharger (the arrangement of the experimental equipment is such that the velocity of the particles in the electrostatic separator vary from approximately 1-2.5 m/s when the velocity in the tribocharger is between 3-15 m/s). For example, a charging velocity of 6.7 m/s produces an absolute

and average charge of $13 \times 10^{-14} \text{C}$ with a standard deviation of $\sigma = \pm 10.9 \times 10^{-14} \text{C}$; whereas a charging velocity of 13.2 m/s produces an absolute and average charge of $30 \times 10^{-14} \text{C}$ with a standard deviation of $\sigma = \pm 49 \times 10^{-14} \text{C}$. The best fit for the charge-velocity relationship is given in the figure as $y(\text{charge}) = -3.94 + 2.59x(\text{velocity})$.

An increasing width in the charge distribution at increased levels of charge accumulated by the silica is not fully understood at the current time but may be related to charge dissipation. Since there is a small ($< 1/5$ second) but probably significant time spent by the particles in the transition zone between the tribocharger and the electrostatic separator, it is possible that charge dissipation occurs and that this dissipation would be more prevalent at higher charging. It is anticipated that as particles are charged to greater values there may be an increasing tendency for the particles to discharge by either particle-particle, particle-wall or other interactions. Future experiments will examine the charge distribution phenomenon to a greater extent.

Figure 3 shows the charge distribution for -200/+325 mesh alumina particles when the velocity in the tribocharger was 6.6 m/s and the electric field intensity was 300 KV/m. Also included in this plot is the Gaussian distribution fit to the data. The average charge accumulated by the alumina under these conditions was $1.3 \times 10^{-14} \text{C}$ ($\sigma = \pm 1.46 \times 10^{-14}$).

In general, it is more difficult to charge the alumina. At velocities near 3 m/s in the tribocharger the average charge accumulated by alumina was approximately zero. Currently we are performing extended experiments to increase the charging velocities

beyond 14 m/s and to develop the charge-velocity relationships for minerals other than silica and for the coals.

Task 3. Sample Characterization

The SEM size distribution analysis of mineral samples has complemented the PDPA analysis. All samples have been subjected to analytical examination to detail their mineralogical constituents.

Task 4. Reports/Publications

A paper entitled "Non-Intrusive Measurement of Particle Charge Relating to Electrostatic Dry Coal Cleaning" was presented at the 1992 Pittsburgh Coal Conference, October 12-16, 1992 in Pittsburgh, PA.

A paper has been accepted for presentation at a conference entitled Coal Utilization and the Environment, May 18-20, 1993. This conference is sponsored by the journal Fuel, and will entail the submission of an article for publication in this journal.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Figure 1. Distribution of charge on 50-70 μm silica spheres; 3.3 m/s charging velocity and 100 kV/m electric field in nitrogen.

Figure 2. The relationship between the charge measured on silica spheres versus the charging velocity; nitrogen atmosphere.

Figure 3. Distribution of charge on -325/+200 mesh alumina particles; charging velocity of 6.6 m/s and 300 kV/m electric field in nitrogen.

END

**DATE
FILMED**

3 / 4 / 93