DOE/PC/90287--T8

25 1992

**OXIDATION OF COAL AND COAL PYRITE
MECHANISMS AND INFLUENCE ON SURFACE CHARACTERISTICS
DE-FG22-90PC90287**

Fiona M. Doyle
University of California at Berkeley
Dept. Materials Science and Mineral Engineering

DOE/PC/90287--T8

DE93 007467

TECHNICAL PROGRESS REPORT (9/30/92)

RESEARCH OBJECTIVES

The objective of this research is to develop a mechanistic understanding of the oxidation of coal and coal pyrite, and to correlate the intrinsic physical and chemical properties of these minerals, along with changes resulting from oxidation, with those surface properties that influence the behavior in physical cleaning processes. The results will provide fundamental insight into oxidation, in terms of the bulk and surface chemistry, the microstructure, and the semiconductor properties of the pyrite.

During the eighth quarter, wet chemical and dry oxidation tests were done on Upper Freeport coal from the Troutville #2 Mine, Clearfield County, Pennsylvania. In addition electrochemical experiments were done on electrodes prepared from Upper Freeport coal pyrite and Pittsburgh coal pyrite samples provided by the U.S. Bureau of Mines, Pittsburgh Research Center, Pennsylvania.

EXPERIMENTAL METHODS AND RESULTS

a. Sample preparation

Monosized fractions of the Upper Freeport coal were prepared using a mortar and pestle, followed by sieving. Both grinding and sieving were done in an argon-filled glove box, to minimize oxidation.

b. Rest Potential Measurements

Coal pyrite electrodes were prepared as reported in our March 1992 report. The potential of Upper Freeport and Pittsburgh coal pyrite electrodes was measured as a function of time for 24 hours, in a pH 7.4 phosphate buffer (0.008695 M KH_2PO_4 , 0.03043 M Na_2PO_4) and a pH 1.0, H_2SO_4 solution. The potentials were measured against a saturated calomel electrode (SCE), using an EG&G Model 273 potentiostat, and then converted to the SHE scale. Table 1 shows the results obtained from the mean of three values for each pyrite electrode. The potentials measured initially were relatively high, then decreased, albeit to different extents. After 24 hours, the potentials were fairly steady. Since there was no oxidant or reductant in the systems, there should not have been any reaction, but the change in potential indicates that some change, either a reaction or a physical

MASTER

ed

Table 1: Potentials of coal pyrite electrodes at pH 1.00 and 7.40.

Sample	pH	Initial Potential, mV SHE	Potential at 24 hr, mV SHE
Upper Freeport coal pyrite	1.00	727 ± 10	311.20 ± 10
	7.40	586 ± 10	303.23 ± 10
Pittsburgh coal pyrite	1.00	645 ± 10	551.50 ± 10
	7.40	730 ± 10	323.30 ± 10

transformation, must have been occurring. Recognizing this, we designate the potential after 24 hours as the "rest potential", with the caveat that this might not be characteristic of true equilibrium.

The Eh-pH diagram for the Fe-S-H₂O systems shown below. The potentials of the Upper Freeport and Pittsburgh coal pyrite samples at each pH have been marked, and designated as UF and P respectively. The subscripts 0 and 24 refer to the potentials at zero and 24 hours. It is clear that in all cases, the potentials of the pyrite samples were well above the region of thermodynamic stability for pyrite. They do not, then appear to correspond to true equilibrium between pyrite and the solutions in which the pyrite is immersed. This non-equilibrium behavior has been reported widely, although there is no consensus on the reasons for these elevated potentials. The pyrite surface may become oxidized during grinding, despite all attempts to exclude oxygen, and form oxide films. Polysulfide films have been observed during oxidation of pyrite in acidic aqueous environments, but are

Eh-pH diagram for the Fe-S-H₂O system at 25°C. Activities of Fe ions: 10^{-1} and 10^{-6} M, sulfur-containing species, 10^{-1} . UF₀ and UF₂₄ denote potentials of Upper Freeport pyrite samples initially, and after 24 hours. P₀ and P₂₄ denote potentials of Pittsburgh pyrite initially and after 24 hours. (Diagram from R.C.H. Ferreira, in *Leaching and reduction in hydrometallurgy*, Ed. A.R. Burkin, Institution of Mining and Metallurgy, London, 1975, pp. 67-83)

unlikely to form on exposure to air, since their formation requires removal of metal ions. Alternatively, the grinding procedure might introduce a large number of defects that alter the stability of the surface layers of pyrite. The initial potentials of the two pyrite samples appear to be fairly similar. Differences are more likely to be due to slight differences in the level of trace oxygen impurities during grinding, or to differences in damage, than to intrinsic characteristics of the pyrite samples. At pH 1, oxide films would be expected to dissolve, which could account for the reduction in potential of both pyrite samples over 24 hours. However, the failure to reach the region of stability for pyrite suggests that there is also some influence from grinding defects, or that a polysulfide layer formed by acid dissolution during the "equilibration" period, and there is a marked difference in the behavior of the Upper Freeport and Pittsburgh coals. Oxide films would not be expected to dissolve at pH 7.4, but oxides could react with the phosphate ions in the buffered system, forming an iron phosphate. This could account for the similarity in "rest potential" for the two pyrite samples.

c. Cyclic Voltammetry Experiments

An Upper Freeport coal pyrite electrode was prepared as previously reported. A Pittsburgh coal pyrite electrode was prepared from a natural crystal, which was dried at 80°C for 30 minutes, then transferred to a vacuum chamber to remove air from the pores. After 10 minutes the sample was coated with a 302-2 epoxy resin, allowing the resin to penetrate all pores. After 20 minutes the crystal was removed from the vacuum chamber, heated at 90°C for 6 hours, then cut to size, avoiding inclusions, cracks and voids.

Because of the porous, irregular nature of the pyrite electrodes, the exposed surface areas were estimated by mapping a magnified image. The estimated areas, 0.2 cm² for the Upper Freeport and 0.187 cm² for the Pittsburgh pyrite, were used to calculate the current densities. Cyclic voltammetry experiments were conducted in a three-compartment Pyrex cell, with a 12 cm² platinum gauze counter electrode, and a saturated calomel reference electrode, using either pH 7.4 phosphate buffer or pH 1.0 H₂SO₄, under argon. The samples were scanned at 20 mV/s for five cycles in each test, starting in the anodic direction from the rest potential. For each pH, voltammograms were obtained after allowing the electrode to equilibrate with the electrolyte solution for both 2 and 24 hours.

Figure 1 shows the cyclic voltammogram of Pittsburgh coal pyrite after contacting for 2 hours with a pH 7.4 phosphate buffer. The cycles are numbered 1-5. On the first cycle, the current was low initially, then increased dramatically at about 0.600 V SHE, and there was a large cathodic peak, I, starting at about -0.3V, with a maximum at -0.48V. This peak decreased in magnitude on subsequent cycles, and was probably due to the reduction of oxidation products that formed during electrode preparation, despite efforts to exclude oxygen. A major cathodic reaction was establishing at -0.65V when the scan direction was reversed back to the anodic direction. From the Eh-pH diagram, it is likely that this was reduction of FeS₂ to FeS, with release of H₂S, although there may only have been partial reduction to a non-stoichiometric sulfide, as proposed by Biegler, 1976:

The anodic peak III is probably due to reversal of this reaction. The size of this anodic peak is less than that of the cathodic peak, because some of the H_2S would diffuse away from the electrode, preventing quantitative re-formation of pyrite. The resulting surface, presumably sub-stoichiometric pyrite, passed a higher anodic current in the potential range 0 - 0.6V than had the original pyrite surface. There was again a large increase in current density, this time at about 0.5V, probably due to the formation of an oxide layer. On the second cycle a cathodic peak started developing at about -0.15V (II), and this increased on subsequent cycles, whereas peak I declined. Peak II would be due to the reduction of the oxide layer that formed at the highest potentials; the fact that this is reduced at a higher potential than the original oxide indicates that it is less stable, possibly a mixed ferrous-ferric oxide or a metastable oxide.

Figure 2 shows the voltammogram of Pittsburgh coal pyrite after 24 hours of contact with pH 7.4 phosphate buffer. The anodic current density is lower than that in Figure 1, and the cathodic peaks I and II did not appear; this suggests that the surface oxide that controlled the behavior in Figure 1 had been replaced by phosphate during conditioning. The phosphate ion would not be reduced at the potentials scanned here, consequently the only cathodic reaction corresponds to the reduction of FeS_2 . Phosphate layers would not have formed, even at the highest potentials scanned in Figure 1, because the low concentration of phosphate in the bulk electrolyte would make transport of phosphate rate-controlling.

Figure 3 shows the cyclic voltammogram obtained with the Pittsburgh coal pyrite electrode after 2 hours of contact with pH 1.0, H_2SO_4 . As in Figure 1, the current density was low on the first anodic excursion; here the current started increasing at about 0.9V. The higher potential is consistent with the lower pH; the Eh-pH diagram shows that for redox reactions involving hydrogen ions, the potential increases with decreasing pH. On reversing the scan direction, the cathodic peak II appeared at about 0.65V, due to reduction of Fe(III) to Fe(II) . This reaction was not seen at pH 7.4 because of the low solubility of iron species. There was no cathodic reaction on the first cycle corresponding to reduction of oxide layers, because these would have dissolved during conditioning. The cathodic reaction occurring at about -0.3V is probably reduction of pyrite (reaction 1 above). Anodic peak III would correspond to reversal of this reaction, and IV is due to oxidation of Fe(II) to Fe(III) . On the second and subsequent cycles, the anodic reaction starting at about 0.85V could be formation of oxide or polysulfide, and the cathodic peak I corresponds to reduction of this.

Figure 4 shows the cyclic voltammogram obtained with Pittsburgh coal pyrite in H_2SO_4 , after equilibrating for 24 hours. The voltammograms are similar to those in Figure 3, in contrast to Figures 1 and 2, where there were significant differences, probably corresponding to replacement of surface oxides by phosphates.

Figures 5 and 6 show cyclic voltammograms obtained with the Upper Freeport coal pyrite electrode after 2 and 24 hours contact with pH 7.4 phosphate buffer. Comparing these figures with Figures 1 and 2, for the Pittsburgh coal under similar conditions, it is clear that the Upper Freeport pyrite is much more "reactive", passing an anodic current at most potentials. During the first cycle a significant cathodic peak was observed, at about -0.65V in

Figure 5, and -0.3V in Figure 6, probably corresponding to reductive dissolution of oxide and oxide-phosphate layers. Anodic conjugate peaks were not observed; instead the anodic current increased steadily, suggesting the reaction of rather poorly crystalline pyrite surfaces. The anodic currents were higher after the first cathodic excursion, probably because the oxide films that dissolved at peaks I had had some passivating influence. The fact that anodic currents continued to pass even when the electrode was being scanned in the cathodic direction demonstrates that the driving force for anodic dissolution was strong enough to continue, even when dE/dt was negative.

d. Dry Oxidation Tests

5g samples of -75 +63 μm Upper Freeport coal, spread to a depth of about 1 mm, were oxidized in a convection oven at 95°C, or at room temperature (mean 21°C) for extensive time periods. Room temperature tests were done with uncontrolled (but low) humidity, dry (in a desiccator), or at 100% humidity (in a desiccator, with the desiccant replaced by water). To avoid oxygen depletion, the desiccators were opened for 30 seconds every 12 hours. The extent of oxidation was assessed by analyzing the carboxylic acid concentration, as described in our December 1991 report, and the flotability of the samples was determined by film flotation tests.

Figure 7 shows that at 95°C there was rapid oxidation in the first few days, followed by steady, but much slower oxidation. At 21°C, there was relatively little oxidation when the samples were dry or under low humidity. At 100% humidity, oxidation appeared to proceed at a steady, intermediate rate for the duration of the test. It appears that water accelerates the oxidation of coal; this could be a physical effect, or could involve surface hydroxyl groups. Figure 8 shows the film flotation partition curves for coal oxidized under the conditions described above. The results are consistent with those in Figure 7; the increase in carboxylic groups produces a slight decrease in the hydrophobicity of the coal samples, but this effect is moderate. None of these oxidation procedures would be expected to have a marked effect on the amenability of Upper Freeport Coal to cleaning by flotation.

e. Wet Chemical Oxidation of Upper Freeport Coal

20g samples of -75 +63 μm Upper Freeport coal were oxidized for 6 hours at room temperature in a well stirred, Pyrex vessel, using 600 ml of 5.0%, 10% and 15% hydrogen peroxide, all at pH 1.0. 10 ml samples of slurry were withdrawn periodically and filtered immediately. The coal was washed to remove residual H_2O_2 , then stored under argon at room temperature. The liquid fractions were stored under argon and refrigerated, then were analyzed by atomic adsorption spectrophotometry to determine the total iron concentration in solution, and hence the extent of pyrite oxidation. The extent of oxidation was assessed by analyzing the carboxylic group concentration, and the flotability of the samples was determined by film flotation tests.

Figure 9 shows the percentage of coal pyrite dissolved by H_2O_2 as a function of time. About 87.49% and 91.85 % of the coal pyrite was dissolved in 6 hours, using 10.0 and 15.0% H_2O_2 respectively, whereas 5.0% H_2O_2 dissolved only about 66.50% of the coal pyrite. Figure

10 shows the variation of solution potential with time. It is clear that the potential increases only marginally with increasing H_2O_2 concentration.

Table II shows the weight percent of carboxylate oxygen generated within 6 hours in each experiment. Comparing with Figure 7, it is clear that the peroxide caused dramatically accelerated oxidation; even 5% H_2O_2 gave more oxidation after 6 hours than occurred in 50 days at 21°C in humid air. This suggests that peroxide is, indeed a suitable oxidant for accelerated oxidation tests. In future, we will perform only limited long-term, simulated weathering tests, and will focus on dilute peroxide to gain a better understanding of oxidation mechanisms. The film flotation partition curves for coal samples oxidized by H_2O_2 are also shown in Figure 8. The use of high concentrations of peroxide strongly decreased the hydrophobicity of coal.

Table II: Weight percent carboxylate oxygen in Upper Freeport coal samples after 6 hours of different oxidation treatments using H_2O_2

Coal Treatment	Weight % carboxylate oxygen
As received coal	0.68%
5.0 % H_2O_2	0.95%
10.0 % H_2O_2	1.20%
15.0% H_2O_2	1.47%

PLANS FOR THE NEXT QUARTER

During the next quarter our studies of the oxidation of Upper Freeport coal will focus on characterization techniques that reveal more about the mechanism of oxidation. These studies will analyze the samples by diffuse reflectance infrared fourier transform analysis (DRIFT), to observe the change in type and relative concentration of surface functional groups, as a function of both time, and nature of oxidant. We will continue to study coal pyrite electrodes, to determine the anodic and cathodic polarization behavior, and cyclic voltammetry in different potential ranges. Because of the complication introduced by using a phosphate buffer, we will also investigate the behavior in a borate buffer.

REFERENCES

T. Biegler, J. Electroanal. Chem., 70, (1976), 265.

Figure 1 : Cyclic voltammogram for Pittsburgh coal pyrite after 2 hours in contact with the electrolyte solution pH 7.4 at 20 mV/s.

Figure 2 : Cyclic voltammogram for Pittsburgh coal pyrite after 24 hours in contact with the electrolyte solution pH 7.4 at 20 mV/s.

Figure 3 : Cyclic voltammogram for Pittsburgh coal pyrite after 2 hours in contact with the electrolyte solution pH 1.0 at 20 mV/s.

Figure 4 : Cyclic voltammogram for Pittsburgh coal pyrite after 24 hours in contact with the electrolyte solution pH 1.0 at 20 mV/s.

Figure 5 : Cyclic voltammogram for Upper Freeport coal pyrite after 2 hours in contact with the electrolyte solution pH 7.4 at 20 mV/s.

Figure 6 : Cyclic voltammogram for Upper Freeport coal pyrite after 24 hours in contact with the electrolyte solution pH 7.4 at 20 mV/s.

Figure 7 : Effect of oxidation time on weight percent oxygen in the form of carboxylic groups on the surfaces of Upper Freeport coal oxidized at 95 C and 21 C

Figure 8 : Film flotation partition curves of Upper Freeport coal samples oxidized at 95 C and 21 C for 35 days, oxidized at 21 C under dry and humid conditions for 50 days and oxidized by 5.0%, 10.0% and 15% H₂O₂ solutions for 6 hours.

Figure 9 : Percentage of coal pyrite dissolved by 5%, 10% and 15% H₂O₂ . 33.33 g/l Upper Freeport coal (200x250 mesh)

Figure 10: Solution potential during oxidation of Upper Freeport coal (200x250 mesh) by 5%, 10% and 15% H₂O₂ .

END

**DATE
FILMED**

3 / 17 / 93