ARGONNE NATIONAL LABORATORY
9700 South Cass Avenue, Argonne, Illinois 60439

ANL/MCT/RP--72673

DE93 006421

Materials and Components Technology Division

Research Summary — 1991

R. W. Weeks, Division Director

W. J. Shack, Associate Division Director

R. A. Valentin, Associate Division Director

Administration:

B. K. Baudino

W. E. Brewer

J. L. Donahue

W. H. Livernash

B. H. Malak

C. A. Malefy

A. C. Smith, Jr.

D. L. Telfer

April 1991

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Contents

Overview of the Materials and Components Technology Division.....	1
Materials Technology.....	5
Ceramics.....	7
Corrosion.....	36
Mechanics of Materials.....	56
Tribology.....	76
Irradiation Performance.....	90
Components Technology.....	97
Superconductivity Applications.....	99
Analytical Thermal-Hydraulics.....	104
Thermal and Mechanical Sciences.....	116
Instrumentation and Nondestructive Evaluation.....	128
Transportation of Hazardous Materials.....	146
APPENDIX A: Regular MCT Employees.....	161
APPENDIX B: Recent and Current Interactions between MCT and Industry.....	165
APPENDIX C: Honors, Awards, and Professional Activities.....	177
APPENDIX D: Other MCT Publications.....	193
Program Index.....	195

Materials and Components Technology Division

Overview of the Materials and Components Technology Division

The Materials and Components Technology Division (MCT) charter is to provide a research and development capability for the design, fabrication, and testing of high-reliability materials, components, and instrumentation. Current divisional programs support the development of the Integral Fast Reactor (IFR); life extension for light water reactors (LWRs); fuels development for the new production reactor and research and test reactors; fusion reactor first-wall and blanket technology; safe shipment of hazardous materials; fluid mechanics, materials, and instrumentation development for fossil energy systems; and energy conservation and renewables technologies, including major efforts in tribology and high-temperature superconductivity.

The MCT Division has approximately 120 regular employees, supplemented annually by more than 150 temporary employees, including visiting faculty members, postdoctoral appointees, graduate and undergraduate students, special term appointees, and visiting industrial personnel on collaborative program assignments. The Division is organized into 10 sections, as shown in the adjacent organization chart; a current listing of regular employees appears in Appendix A. A listing of recent and ongoing programmatic interactions with industry is included in Appendix B. Recent awards and professional activities of staff members are listed in Appendix C.

As shown below, financial support for MCT programs comes primarily from the Nuclear, Conservation and Renewables, Fossil, Fusion, and Environment, Safety and Health offices of the U.S. Department of Energy (DOE), and from the U.S. Nuclear Regulatory Commission. Additional efforts are funded by the Department of Defense, the National Park Service, private industry, public utilities, the National Science Foundation, and the DOE Office of Basic Energy Sciences. Total funding for the Division in FY 1991 is approximately \$22 million.

Since the last issue of this report in 1989, two events have had important impacts on the Division. The increased emphasis on environment, safety and health (ESH) issues by DOE culminated in a "Tiger Team" review of Argonne National Laboratory (ANL) in 1990. As a result, ANL and its divisions have taken many steps to ensure that all programs comply with current laws, regulations, and policies regarding ESH and quality assurance matters. The second event was the reorganization of the IFR program at ANL in 1990 to consolidate the IFR design effort. This resulted in the transfer of 17 MCT people involved in IFR design work to a new Reactor Engineering Division. Publications produced by these individuals before their transfer are listed in Appendix D.

MCT Funding Sources for FY 1991

Ongoing MCT programs are summarized below; more detailed discussions are included in the Section reports that follow. Because several sections usually participate in each program area, an index by program area is included at the end of this book.

Fission Reactors

MCT is part of a multidivisional effort at Argonne to develop the IFR concept that will be demonstrated at ANL's EBR-II reactor site in Idaho. MCT is involved in fuel development efforts that include computer modeling of fuel element performance, fuel behavior testing under normal and off-normal reactor conditions, and in-pile testing of IFR fuel elements. Work on design of a cathode processor for the IFR fuel cycle facility, sodium pump testing, and IFR seismic design studies was transferred to the new Reactor Engineering Division.

Plant life extension for commercial LWRs involves a number of materials and components issues. MCT is investigating phenomena such as stress corrosion cracking, erosion and corrosion, embrittlement, fatigue, and flow distributions and flow-induced vibrations, together with modeling of fission-product behavior under accident conditions and component failure analyses (including Three Mile Island Unit 2 components), that will have significant effects on plant life extension.

The MCT Division is conducting environmental tests of structural materials, together with safety studies related to fuel behavior under postulated accident conditions, for the new defense production reactor. In addition, MCT staff are developing fuels for the Advanced Neutron Source at Oak Ridge National Laboratory and are assessing fuel concepts for space nuclear applications.

Fusion Technology

The Division participates in design studies for magnetic-confinement fusion reactors through thermomechanical analyses of reactor components, and through materials testing. The latter includes vanadium alloy development with studies of radiation effects and compatibility with lithium, together with determination of tritium release kinetics from solid breeder materials.

Transportation of Hazardous Materials

The Department of Energy is responsible for numerous shipments of nuclear and other potentially hazardous materials by all types of transport. To ensure the safe handling of these materials, detailed Safety Analysis Reports for Packaging (SARPs) are required. MCT reviews these reports technically and recommends whether Certificates of Compliance should be issued. This work is coordinated with the Nuclear Regulatory Commission and the U.S. Department of Transportation. The Division also conducts workshops to inform applicants of requirements, and it produces films and videotapes to educate the public about the procedures used to ensure safe transport of hazardous materials.

Conservation and Renewables

Fabrication of optimized conductors made from high-temperature superconducting (HTSC) materials is a major research area for MCT, along with device development for early commercialization of this technology. Bulk and thin- and thick-film configurations are all included in the program, which is carried out in close cooperation with industry, and a variety of high-temperature superconducting materials are employed. The Division is also responsible for the Argonne Superconductivity Pilot Center, which supports joint work with industry to develop early applications of this technology. Ongoing efforts include work on optimized conductors, sensors, magnetic bearings, current leads, and superconducting motors. An HTSC Processing Center is also operated by the Ceramics Section to train students and visiting faculty to work with these new materials. About 50 students work in the Center each year.

The DOE National Tribology Program is managed by the Tribology Section in MCT. This program, which is carried out cooperatively at a variety of industrial, government, and university laboratories, is aimed at developing enabling technology for high-temperature, low-heat-rejection engines. The work includes development of materials that exhibit low friction and wear properties, synthetic lubricants to extend the temperature range of liquid lubricants, vapor-phase delivery systems, and coating technology for very-high-temperature solid lubricant applications. Tribological data bases for use by industry have been developed under the auspices of the national program. MCT carries out in-house tribology research to develop low-friction, wear-resistant surfaces and coatings by processes such as ion-beam-assisted-deposition. New concepts are tested in the Division's tribological testing laboratory, and the laboratory tests are supplemented by instrumented engine testing.

State-of-the-art nondestructive evaluation (NDE) techniques are being developed to improve the fabrication technology for ceramic and composite materials and to determine the integrity of components made from these materials. These NDE techniques include nuclear magnetic resonance imaging for density distributions, as well as microfocus X-rays for defect identification. The Intense Pulsed Neutron Source at ANL is used for residual stress analyses, and thermal wave imaging is under development for determining the reliability of coatings.

To reduce the use of refrigerants that are destructive to the ozone layer or that contribute to the "greenhouse" effect, small compact heat exchangers are under development to replace larger, less efficient ones. This requires new design correlations for pressure drop and heat transfer, and these are being developed in the Thermal and Mechanical Sciences Section. Improved heat transfer is also the goal of a program that is investigating friction-reducing fluid additives and phase-change slurries.

A joint venture with industry is underway to develop a predictive model for mold filling and solidification of metal castings. The program will operate on an engineering workstation and should allow improved mold design in less time than is required with current empirical techniques.

Additional conservation efforts include a cooperative program with industry for developing improved refractories for steelmaking, and component reliability testing for a sodium heat engine.

Fossil Energy

The MCT Division carries out a variety of base-technology and end-use-specific work in support of fossil energy systems. The supporting base technology includes development of structural ceramics with improved fracture toughness, NDE techniques to evaluate these materials, sulfidation-resistant alloys and coatings, and advanced instrumentation for process control. A new initiative will develop a more fundamental understanding of solid/liquid slurry flows. End-use-specific work includes joint projects with industry on the development of solid-oxide fuel cells (in cooperation with the ANL Chemical Technology Division), improved ceramic filters for hot gas cleanup, alloy testing and selection for advanced fluidized bed and magnetohydrodynamic systems, and acid rain effects on materials.

Other

The Division conducts basic studies on flow-induced vibrations, as well as cooperative materials work (with the Materials Science Division) in pursuit of a basic understanding of high-temperature superconductors. In addition, MCT has several specific projects aimed at developing arms control technology.

Materials Technology

Ceramics

Section Manager: R. B. Poeppel

Principal Investigators: U. Balachandran, S. E. Dorris, K. C. Goretta, M. T. Lanagan,

P. S. Matya, J. P. Singh, C. A. Youngdahl

Support Staff: J. T. Dusek,¹ J. J. Picciolo

Technicians: J. E. Emerson, R. L. McDaniel

Secretary: S. M. Hagamann²

Students: A. Blondo,³ T. Brent,⁴ C. Y. Chu,³ J. Creech,⁵ K. Hearley,⁶ J. Joo,³

K. S. Kirkpatrick,⁷ M. McMann,⁵ S. Morissette,⁸ G. Risch,⁹ R. Russell,⁶ R. J. Sayre,⁵

T. Suratwala,⁶ W. Wu,¹⁰ C.-T. Wu,³ D. Xu¹¹

The Ceramics Section is responsible for a wide range of programs dealing with the selection, synthesis, fabrication, characterization, testing and application of ceramic materials. Staff members work equally well in lead and support roles. The majority of the work is done on projects for which the Section has the lead. In terms of number of projects, however, the Section participates in many more in which it plays a supporting role. The programmatic base has increased significantly since the last review in 1989. We have developed several new High-Temperature Superconductivity Pilot Center projects and we have assumed responsibility for the total Pilot Center Program. Other new projects include work on ceramic containment for actinide separation on ceramic filters for coal gasification, on sodium β -alumina for sodium heat engines, on novel oxygen ion conductors for converting methane to ethane by controlled oxidation, and on characterization of fiber/matrix bonding in ceramic-ceramic composites.

Experimental capability has also increased. Many additional furnaces, additional cryogenic electrical characterization capability, and an X-ray diffractometer have been set up. A new Instron was purchased and installed. We are formulating plans for a renovation of our office and laboratory areas to relieve deficiencies in the heating and ventilating, water supply, sewer, and electrical systems while streamlining traffic patterns and enhancing space utilization. We have instituted regular weekly safety meetings and are working hard to ensure that our area is in compliance with DOE and Laboratory ES&H requirements.

¹Special Term Appointee.

²Serves two sections.

³Illinois Institute of Technology.

⁴Purdue University.

⁵Clemson University.

⁶University of Illinois at Urbana-Champaign.

⁷Northwestern University.

⁸DePaul University.

⁹University of Cincinnati.

¹⁰University of Illinois at Chicago.

¹¹San Jose State University.

High-Temperature Ceramic Superconductors

The Ceramics Section has achieved worldwide recognition for its work in the fabrication of high-temperature ceramic superconductors. We have consistently been able to deliver on promises to supply material for many diversified collaborations focused on the development of practical commercial applications, as well as on studies of the basic properties of the materials.

Under a reorganization mandated by DOE, we have combined the former STEPS program (Superconductor Technology for Electric Power Systems) and the ANL Pilot Center for the rapid commercialization of high-temperature superconductivity. The combined program will enable us to focus our industrial collaborations more directly on DOE's programmatic needs. Pilot center projects will be supported on the basis of their fulfillment of one of two basic attributes: (1) how they contribute to the long-term goal for developing conductors for electric power applications and (2) their ability to use high-temperature superconductors available in the immediate future in practical, although perhaps limited, applications.

Technical progress in developing high-critical-temperature materials continues to be very encouraging. The Section is working with the three basic classes of material that superconduct above 77 K, the boiling point of liquid nitrogen. These are (1) the $\text{YBa}_2\text{Cu}_3\text{O}_7$ system, or 123, in which Y can be replaced by almost any rare-earth element or by combinations of rare earths, any of which has a critical temperature (T_c) of ≈ 93 K; (2) the bismuth-strontium-calcium-copper oxide system, including those formulations in which some of the bismuth is replaced by lead to promote formation of the phase with a T_c of 110 K; and (3) the thallium-calcium-barium-copper oxide system, including the composition which superconducts at 125 K -- the highest confirmed T_c .

Progress has been achieved in synthesizing these materials. We have learned that a reduced oxygen pressure leads to drastically reduced synthesis time and temperature for the 123 materials and we are now developing these procedures to synthesize the bismuth and thallium materials. Other progress has come in the area of mechanical properties. By incorporating metallic silver particles or ZrO_2 into the 123 microstructure, we improved fracture toughness by a factor of 3 and fracture stress by a factor of 2. Neutron diffraction and stress analysis of the 123/silver composites indicate that the silver is in tension, which places the brittle ceramic in compression in the composite structures.

Structural Ceramics and Composites

Initiation of a fracture in a structural ceramic can often be traced to a preexisting flaw that was inadvertently introduced during fabrication. In a long-standing collaborative effort with the Instrumentation and Nondestructive Evaluation Section, the Ceramics Section is characterizing the fracture behavior of structural ceramics and composites containing well-defined flaws. Samples of silicon nitride and its composites with Si_3N_4 -whisker reinforcement have been fabricated by both cold and hot pressing with appropriate additives. The fracture stress, fracture toughness, and elastic modulus of these samples are being evaluated and correlated with the fractographically located critical flaws to establish the effects of the flaws. We are evaluating these ceramics and composites in both green

(cold-pressed) and fired states in an attempt to find correlations between flaw population (strength distribution) of green specimens and the corresponding densified specimens. Understanding the effects of these flaws on fracture behavior will help in development of ceramic and composites that have improved mechanical properties. The results are being used by the Instrumentation and Nondestructive Evaluation Section to guide the development of nondestructive testing methods. In a related program, we are evaluating how the mechanical properties of ceramic matrix composites are affected by the interfacial properties between ceramic whiskers (or continuous fibers) and matrix. The interface characteristics between the ceramic matrix and whisker/fiber are evaluated by scanning electron microscopy and are correlated with the mechanical properties (strength, toughness) of composites. These correlations will provide information for designing and developing appropriate interface characteristics for thorough control of processing parameters. The results of this study will help develop ceramic composites with improved properties.

Solid Oxide Fuel Cells

Development of all-ceramic fuel cells employing yttria-stabilized zirconia as the electrolyte has been carried out in concert with ANL's Chemical Technology Division. The goal is to produce a compact and lightweight fuel cell array that can operate on a wide range of fossil fuels. In addition to the zirconia electrolyte, the fuel cell has three other ceramic components: (1) a strontium-doped lanthanum chromite interconnect, (2) a strontium-doped lanthanum manganite cathode, and (3) a cermet anode fabricated from a mixture of nickel and yttria-stabilized zirconia. These components have been formed into thin sheets and laminated into a honeycomb structure with open channels 0.040 to 0.050 in. wide. The channels allow fuel and air to flow to the active cell areas. The emphasis in the present program is to evaluate the effects of dopant on the sintering kinetics of the interconnect. Support for this program is from the DOE Office of Fossil Energy, subcontracted through Allied Signal, Inc. This funding arrangement promotes the transfer of this technology to the private sector.

Sodium Heat Engine

A program has been initiated to improve the performance of the sodium heat engine, a thermoelectric device that uses the Na-ion conductor β'' -alumina. Performance of the sodium heat engine has been limited to date by premature mechanical failure of the β'' -alumina electrolyte tubes, but should improve when premature breakage of the electrolyte tubes is reduced. The program at ANL examines possible causes of failure and how to eliminate or minimize these failures. The stresses that develop during operation of the heat engine are being modeled to ensure that the operating procedures do not inadvertently subject the electrolyte tubes to excessive stress. The mechanical properties of present-day commercial tubes are being characterized to determine if they can withstand typical operating stresses. Nondestructive techniques are being evaluated to screen tubes with large life-limiting flaws and thereby eliminate weak tubes. Beside attempting to improve the performance of present-day commercial electrolytes, we are exploring alternative processing techniques as a means of improving the properties of the β'' -alumina tubes.

Refractories Research

The Section is renewing its efforts in advanced refractory materials for iron and steelmaking. A recent small program funded by Magneco/Metrel and the State of Illinois is aimed at developing castable refractories based on sol-gel technology for a variety of uses, primarily in iron- and steelmaking with improved corrosion and thermal stress properties. Uses would include ladles, ladle treatment vessels, and furnace linings. Refractories with various compositions are fabricated at Magneco/Metrel with different heat treatments. Subsequently, the microstructure, phase composition, and corrosion properties of these refractories are evaluated at ANL. A correlation between microstructure and properties provides information for optimizing refractory compositions with improved properties. Magneco/Metrel is a major supplier of refractory castables for the continuous casting of steel; it supplies castable refractories for other industries as well. In cooperation with Magneco/Metrel, the Section is preparing proposals for follow-on work. This work will rely on expertise and facilities established in the Section during a long-funded program to support refractories development for slagging coal gasifiers.

Materials Development Work for Actinide Recycle Project

The processes for the recovery of actinides from light water reactor (LWR) fuels for use in the Integral Fast Reactor (IFR) require containment vessels, stirrers, filters, and transfer tubing. For these processes, calcium is used as the reductant to reduce oxide fuel and many of the fission products. Reduction is followed by operations to separate uranium from other actinides and to recover reagents and minimize wastes. The liquid metal solvents, such as copper-magnesium and zinc-magnesium, cadmium, and molten calcium and alkaline earth halide salts, used in the processing of actinides must not react with containers and other components. In addition, for repeated use of the containers and components, these metals, salts, and radioactive materials should not wet them; the materials also should withstand high temperatures, should be chemically stable, possess good mechanical properties, and have good thermal shock resistance. The materials should be sufficiently dense or porous, depending on the specific applications, and still have the mechanical integrity needed in the aggressive chemical and thermal environments. The technology for component fabrication should allow scale-up from laboratory to commercial level.

Candidate materials for high-temperature operations can be either refractory metals or ceramics of appropriate compounds or metal-oxide composites (cermets). The ceramic container materials currently being considered for evaluation of mechanical properties and corrosion resistance include oxides and nitrides with very low free energy of formation, namely, magnesium oxide, calcium zirconate, calcium yttrate, aluminum nitride, and titanium nitride. The Ceramics Section is developing these materials and fabricating test crucibles for possible actinide processing. Candidate materials are exposed to molten calcium and salt for assessment of possible chemical interactions. Preliminary screening experiments on test crucibles suggest that (1) some impurities, such as aluminum in the grain boundaries of calcium zirconate, have deleterious effects on corrosion and (2) calcium yttrate is much more resistant to corrosion in molten calcium than is calcium zirconate. This materials development work is being performed in cooperation with the Chemical Technology Division.

Laboratory Exchange Program

We continue to be a strong supporter of ANL's laboratory exchange program. Under this program, selected scientists from the research laboratories of major U.S. corporations spend a year at ANL. After the highly successful term of Dr. Keith Karasek (Allied Signal Corp.), Dr. Marc Kullberg of Amoco has just completed a successful term at ANL. During his tenure, Dr. Kullberg fabricated high- T_c superconducting films by a sol-gel method. Our collaboration has produced two coauthored publications; we are continuing this collaboration and extending the sol-gel process to other systems. This year, Mr. Mike Anderson of Magneco/Metrel has joined the Ceramics Section. His extensive experience in refractory fabrication will be applied in the development of refractories with improved mechanical and corrosion properties. Mr. Anderson will gain experience in microstructural evaluation and its correlation with refractory properties, which will be very valuable for refractory development at Magneco/Metrel.

Recent Work by the Ceramics Section

Publications

X-Ray Diffraction and Vibrational-Spectroscopy Study of the Structure of $\text{La}_2\text{Ti}_2\text{O}_7$

U. Balachandran and N. G. Eror (Oregon Graduate Center)

J. Mater. Res. 4(6), 1525-1528 (November/December 1989).

Processing Y- and Bi-based Superconductors

U. Balachandran, D. I. Dos Santos, A. W. von Stumberg, S. W. Graham, J. P. Singh, C. A.

Youngdahl, K. C. Goretta, D. Shi, and R. B. Poeppel

INVITED PAPER: Proc. Xth Winter Meeting on *Low Temperature Physics*, Cocoyoc, Morelos, Mexico, January 16-18, 1989, ed. T. Akachi, J. A. Cogordan, and A. A. Valladares, World Scientific, Teaneck, NJ, 1989, Vol. 20, pp. 129-138.

Sintering $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_y$ Pellets and Thick Films

U. Balachandran, M. T. Lanagan, M. C. Einloth, J. P. Singh, K. C. Goretta, and R. B. Poeppel

Presented at 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 152.

Microstructure and Superconductivity in $\text{YBa}_2\text{Cu}_{3+x}\text{O}_8$

U. Balachandran, C. D. Talsma, S. E. Dorris, D. Shi, R. B. Poeppel, and T. O. Mason (Northwestern University)

Presented at the Fall Mtg. of the Materials Research Soc., Boston, MA, November 27-December 2, 1989.

Processing and Fabrication of $\text{YBa}_2\text{Cu}_4\text{O}_x$ and $\text{YBa}_2\text{Cu}_4\text{O}_x/\text{YBa}_2\text{Cu}_3\text{O}_y$ Composites

U. Balachandran, M. E. Biznek, K. C. Goretta, D. Shi, R. B. Poeppel, and T. O. Mason (Northwestern University)

Presented at the Fall Mtg. of the Material Research Soc., Boston, MA, November 27-December 2, 1989.

BOOK REVIEW: *Materials Research Society Symposia Proceedings, Vol. 82: Characterization of Defects in Materials*, edited by R. W. Siegel, J. R. Weertman, and R. Sinclair

U. Balachandran

Submitted to Ceram. Abstr.

Material and Fabrication Challenges in the Development of Monolithic Solid Oxide Fuel Cells

U. Balachandran, S. E. Dorris, J. J. Picciolo, R. B. Poeppel, C. C. McPheeters (CMT), and N. Q. Minh (Allied-Signal Aerospace Company)

To be published in Proc. 24th Intl. *Energy Conversion Engineering Conf.*, Washington, DC, August 6-11, 1989.

Microstructure and Electrical Properties of Bulk High- T_c Superconductors

U. Balachandran, M. J. McGuire, K. C. Goretta, C. A. Youngdahl, D. Shi, and R. B. Poeppel

To be published in Proc. 3rd Ann. Conf. on *Superconductivity and Applications*, Buffalo, NY, September 19-21, 1989.

Synthesis of 80 K Superconducting $\text{YBa}_2\text{Cu}_4\text{O}_8$ via a Novel Route

U. Balachandran, M. E. Blznek, G. W. Tomlins, B. W. Veal, and R. B. Poeppel
 Phys. C. 165, 335-339 (January 1990)

Synthesis of Phase-Pure Orthorhombic $\text{YBa}_2\text{Cu}_3\text{O}_x$ under Low Oxygen Pressure

U. Balachandran, R. B. Poeppel, J. E. Emerson, S. A. Johnson (CMT), M. T. Lanagan, C. A. Youngdahl, D. Shi, K. C. Goretta, and N. G. Eror (Oregon Graduate Center)
 Mater. Lett. 8(11,12), 454-456 (November 1989).

Synthesis of Superconducting Phase-Pure $\text{YBa}_2\text{Cu}_4\text{O}_8$

U. Balachandran, M. E. Bisnek, G. W. Tomlins, B. W. Veal, and R. B. Poeppel
 Presented at the 1990 TMS Ann. Mtg. Exhibition, Anaheim, CA, February 19-21, 1990.

Practical Superconductor Development for Electrical Power Applications, Annual Report for FY 1988

U. Balachandran, I. D. Bloom (CMT), S. E. Dorris, J. T. Dusek, J. E. Emerson, K. C. Goretta, K. E. Gray, J. R. Hull, R. T. Kampwirth, M. T. Lanagan, H. J. Leu, V. A. Maroni, R. L. McDaniel, J. J. Picciolo, J. P. Singh, L. R. Turner, and C. A. Youngdahl
 ANL-88-37 (February 1989).

Sintering $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_y$ Pellets and Thick Films

U. Balachandran, M. T. Lanagan, M. C. Einloth, J. P. Singh, K. C. Goretta, and R. B. Poeppel
 To be published in Proc. 1st Intl. *Ceram. Science and Technology* Congress, Anaheim, CA, October 31-November 3, 1989.

Hot Extrusion of High-Temperature Superconducting Oxides

U. Balachandran, K. C. Goretta, R. B. Poeppel, and J. G. Hunt (Atek Metals Center, Inc.)
 To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Development of Interconnect Material for Monolithic Solid Oxide Fuel Cell Stacks

U. Balachandran, J. J. Picciolo, S. E. Dorris, C. C. McPheeters (CMT), D. W. Dees (CMT), and R. B. Poeppel
 To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Formation of Ruddlesden-Popper Phases in Doped Perovskites

U. Balachandran and N. G. Eror (University of Pittsburgh)
 To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Synthesis of 80 K $\text{YBa}_2\text{Cu}_4\text{O}_8$ Superconductor

U. Balachandran, B. W. Veal, H. Shi, and R. B. Poeppel
 To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Processing and Fabrication of $\text{YBa}_2\text{Cu}_4\text{O}_8$ and $\text{YBa}_2\text{Cu}_4\text{O}_8/\text{YBa}_2\text{Cu}_3\text{O}_x$ Composites

U. Balachandran, M. E. Biznek, K. C. Goretta, B. W. Veal, and R. B. Poeppel

To be published in Proc. Fall Mtg. of the Material Research Soc., Boston, MA,
November 27-December 2, 1989.

Synthesis of Ceramic Superconductors under Low Oxygen Pressure

U. Balachandran, R. B. Poeppel, J. E. Emerson, M. T. Lanagan, C. A. Youngdahl, and S. A. Johnson (CMT)

To be published in Proc. Intl. Conf. on *Superconductivity*, Bangalore, India, January
10-14, 1990.

Synthesis of Superconducting Phase-Pure $\text{YBa}_2\text{Cu}_4\text{O}_8$

U. Balachandran, M. E. Bisnek, G. W. Tomlins (MSD), B. W. Veal (MSD), and R. B. Poeppel

High Temperature Superconducting Compounds II, ed. S. H. Whang, A. DasGupta,
and R. Laibowitz, (Proc. 1990 TMS Symp. on *High Temperature Superconducting
Compounds*, Anaheim, CA, February 19-21, 1990), The Minerals, Metals and
Materials Society, Warrendale, PA, 1990, pp. 129-138.

Degradation of Properties of YBCO Superconductors Sintered in CO_2 -Containing Atmosphere

U. Balachandran, C. Zhang, Y. Gao, (MSD), Y. Li (MSD), K. L. Merkle (MSD), J. N. Mundy
(MSD), B. W. Veal (MSD), R. B. Poeppel, and G. Selvaduray (San Jose State University)

To be presented at 4th Ann. Conf. on *Superconductivity and Applications*, Buffalo,
NY, Sept. 18-19, 1990.

Improved Processing and Fabrication of Ceramic Superconductors

U. Balachandran and R. B. Poeppel

To be presented at Pilot Center Industrial Overview Committee Mtg., Argonne
National Laboratory, Argonne, IL, May 8-9, 1990.

Improved Synthesis of YBCO Superconductors

U. Balachandran, S. E. Dorris, J. Michiels, and R. B. Poeppel

To be presented at 43rd Pacific Coast Regional Meeting of the American Ceramic
Society, Seattle, WA, Oct. 25-27, 1990.

Preparation and Characterization of $\text{YBa}_2\text{Cu}_4\text{O}_8$ Superconductor

U. Balachandran, B. W. Veal (MSD), K. L. Merkle (MSD), Y. Cao (MSD), R. B. Poeppel, R.
K. Williams (Oak Ridge National Laboratory), and D. Kroeger (ORNL)

To be presented at 2nd Intl. Sci. and Techn. Congress and the American Ceramic
Society's Electronics Div. Mtg. Orlando, FL, Nov. 12-15, 1990.

Preparation of YBCO Superconductor via Ternary Precursors

U. Balachandran, R. A. Russell, and R. B. Poeppel

Submitted to the 2nd Intl. *Ceram. Sci. and Tech.* Congress and Amer. Ceram. Soc.
Electronics Div. Mtg., Orlando, FL, Nov 12-15, 1990.

Synthesis of 80 K YBa₂Cu₄O₈ Superconductor under Reduced Oxygen Pressure

U. Balachandran, B. W. Veal, H. Shi, and R. B. Poeppel

Presented at NSF/Science and Technology Center for Superconductivity Workshop on *Processing of Superconductors*, Argonne National Laboratory, Argonne, IL, June 12, 1990.

Improved Synthesis and Fabrication of High Temperature Superconductors

Balachandran, U.

Presented at the Naval Surface Warfare Center, Silver Spring, MD, May 30, 1990.

Effects of Atmosphere and Heating Rate during Processing of a Ceramic Superconductor

U. Balachandran, D. Xu, C. Zhang, S. E. Dorris, R. A. Russell, J. T. Dusek, J. J. Picciolo, R. B. Poeppel, and G. Selvaduray (San Jose State University)

INVITED PAPER to be presented at 3rd Intl. Symp. on *High-Temp.*

Superconductors: Processing and Microstructure Property Relationships, 1991 TMS Annual Mtg., New Orleans, LA, Feb. 17-21, 1991.

Formation of Intermediate Compounds during Reduced-Pressure Calcination of YBCO Precursor

U. Balachandran, S. L. Morissette, R. A. Russell, S. E. Dorris, and R. B. Poeppel

To be presented at 3rd Intl. Symp. on *High Temp. Superconductors: Processing and Microstructure Relations*, 1991 TMS Annual Mtg., New Orleans, LA, Feb. 17-21, 1991.

Microstructure and Electrical Properties of Bulk High-T_c Superconductors

U. Balachandran, M. J. McGuire, K. C. Goretta, C. A. Youngdahl, D. Shi (MSD), R. B. Poeppel, and S. Danyluk (University of Illinois at Chicago)

Superconductivity and Application, ed. H. S. Kwok, et al., Proc. 3rd Ann. Conf. on *Superconductivity and Applications*, Buffalo, NY, Sept. 19-21, 1989, Plenum Press, New York, 1990, pp. 265-271.

Review of the book "Ceramic Transactions, Vol. 5: Advanced Characterization Techniques for Ceramics," edited by W. S. Young, G. L. McVay, and G. E. Pike

U. Balachandran

Ceramic Abstracts, American Ceramic Society.

Degradation of Properties of YBa₂Cu₃O_x Superconductors Sintered in CO₂-Containing Atmosphere

U. Balachandran, Z. Zhang, D. Xu, Y. Gao (MSD), K. L. Merkle (MSD), J. N. Mundy (MSD), B. W. Veal (MSD), R. B. Poeppel, G. Selvaduray (San Jose State University) and T. O. Mason (Northwestern University)

To be published in Proc. 4th Ann. Conf. on Superconductivity and Applications, Buffalo, NY, Sept. 18-20-1990.

Controlled Removal of Processing Aids from Ceramic Tapes

U. Balachandran, S. E. Dorris, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel

To be presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc., Cincinnati, OH, Apr. 28-May 2, 1991.

Effects of Atmosphere during Processing of YBCO Superconductor

U. Balachandran, S. E. Dorris, R. A. Russell, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel
 To be presented at 1990 *Materials Research Society* Fall Mtg., Boston, MA, Nov. 26
 - Dec. 1, 1990.

Mechanical Properties and Deformation of Polycrystalline Lithium Orthosilicate

K. Bär (Institute of Reactor Materials, FRG), C. Y. Chu (Illinois Institute of Technology),
 K. C. Goretta, J. L. Routbort, M. C. Billone, and R. B. Poeppel
 Fusion Engineering and Design 8, 371-374, (1989) North-Holland, Amsterdam.

Texture Characterization of High- T_c Thick Films

A. C. Blondo (Illinois Institute of Technology), J. S. Kallend (IIT), R. B. Poeppel, M. T.
 Lanagan, and T. C. Schofield (Los Alamos National Laboratory)
 To be presented at 23rd Intl. Symp. on ISHM '90, Chicago, IL, Oct. 13-17, 1990.

Texture Characterization of High- T_c Thick Films

A. C. Blondo (Illinois Institute of Technology), J. S. Kallend (IIT), R. B. Poeppel, M. T.
 Lanagan, and T. C. Schofield (Los Alamos National Laboratory.)
 To be published in Proc. 23rd Intl. Symp. on *Microelectronics*, Chicago, IL, Oct.
 13-17, 1990.

Effect of Heat Treatment Time and Temperature on the Properties of $YBa_2Cu_3O_{7-x}$

I. Bloom (CMT), B. S. Tani (CMT), M. C. Hash (CMT), D. Shi, M. A. Patel, K. C. Goretta,
 N. Chen, and D. W. Capone (Supercon, Inc.)
 J. Mater. Res. 4(5), 1093-1098 (September/October 1989).

Slip Casting High- T_c Superconductors

D. E. Bloomberg, D. S. Applegate, T. L. Tolt (Case Western Reserve University), M. T.
 Lanagan, J. T. Dusek, R. B. Poeppel, and K. C. Goretta
 J. Mater. Sci. Lett. 8, 759-761 (1989).

Radio Frequency Surface Resistance of Large-Area Bi-Sr-Ca-Cu-O Thick Films on Ag Plates

C. L. Bohn (EP), J. R. Delayen (EP), U. Balachandran, and M. T. Lanagan
 Appl. Phys. Lett. 55(3), 304-306 (July 1989).

Influence of Oxygen Concentration on Processing $YBa_2Cu_3O_{7-x}$

N. Chen, D. Shi, and K. C. Goretta
 J. Appl. Phys. 66(6), 2485-2488 (15 September 1989).

Mechanical Properties of Polycrystalline Lithium Orthosilicate

C. Y. Chu (Illinois Institute of Technology), K. Bär (Institute of Reactor Materials, FRG),
 J. P. Singh, K. C. Goretta, M. C. Billone, R. B. Poeppel, and J. L. Routbort
 INVITED PAPER published in J. Am. Ceram. Soc. 72(9), 1643- 1648 (1989).

Mechanical Properties and Microstructure of Si_3N_4 -Whisker-Reinforced Si_3N_4 Matrix Composite

C. Y. Chu and J. P. Singh

To be presented at the 14th Ann. Conf. on *Composites and Advanced Ceramics*, Cocoa Beach, FL, January 14-17, 1990.

Observations on the Microstructures of Hot-Pressed Si_3N_4 and Whisker-Reinforced Si_3N_4 Matrix Composites

C. Y. Chu and J. P. Singh

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Mechanical Properties and Microstructure of Si_3N_4 -Whisker-Reinforced Si_3N_4 Matrix Composite

C. Y. Chu (Illinois Institute of Technology) and J. P. Singh

To be published in Proc. 14th Ann. Conf. on *Composites and Advanced Ceramics*, Cocoa Beach, FL, January 14-17, 1990.

Relationship between Fabrication Parameters and Structural Characteristics of Sintered Lithium Orthosilicate

C. Y. Chu (Illinois Institute of Technology), K. Bär (Institute of Reactor Materials, FRG), J. P. Singh, R. B. Poeppel, and M. C. Billone

Fusion Engineering and Design 8, 375-378, (1989) North-Holland, Amsterdam.

Microstructures and Toughening of Si_3N_4 -Whisker-Reinforced Si_3N_4 Matrix Composites

C-Y Chu and J. P. Singh

To be presented at Amoco/University Poster Session, Naperville, IL, Oct. 5, 1990.

High-Temperature Microstructure and Strength of Hot-Pressed Si_3N_4 and Whisker-Reinforced Si_3N_4 Matrix Composites

C. Y. Chu, J. P. Singh, and J. L. Routbort (MSD)

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc., Cincinnati, OH, Apr. 28-May 2, 1991.

Impedance Spectra during Solid State Powder Reactions of Oxide Superconductors

E. A. Cooper (Northwestern U.), T. O. Mason (Northwestern U.), M. E. Biznek, and U. Balachandran

J. Am. Ceram. Soc. 73(1), 154-157 (January 1990).

High- T_c Oxide State Reaction Kinetics via Complex Impedance Spectroscopy

E. A. Cooper (Northwestern University) T. O. Mason (NU.), U. Balachandran, and M. L. Kullberg (Amoco Chemical Co.)

To be published in Proc. Materials Research Society Fall Mtg., Boston, MA, Nov. 27-Dec 2, 1990.

Electrical Characterization during Reactions of Superconductor Oxide Precursors.

E. A. Cooper (Northwestern University), T. O. Mason, (NU.), U. Balachandran, and R. B. Poeppel

To be presented at 2nd Intl. *Ceramic Science and Technology* Congress and The American Ceramic Society's *Electronics Div. Mtg.*, Orlando, FL, Nov. 12-15, 1990.

High- T_c Solid State Reaction Kinetics via Complex Impedance Spectroscopy

E. A. Cooper (Northwestern University), T. O. Mason (NU), U. Balachandran, and M. L. Kullberg (Amoco Chemical Co.)

To be published in Proc. Fall Mtg. Material Research Society, Boston, MA, Nov. 27-Dec. 2, 1990.

Compressive Creep of SiC-Whisker Reinforced Al_2O_3

Antonio R. de Arellano-López (Universidad de Sevilla, Spain), Francisco L. Cumbreira (U. de Sevilla), and Arturo Domínguez-Rodríguez (U. de Sevilla), Kenneth C. Goretti, and Jules L. Routbort (MSD)

J. Am. Ceram. Soc. 73(5), 1297-1300 (1990).

High-Temperature Compressive Deformation of SiC-Whisker Reinforced Al_2O_3

A. R. de Arellano-Lopez (Universidad de Sevilla, Spain), A. Domínguez-Rodríguez (U. de Sevilla), K. C. Goretti (MCT), and J. L. Routbort

Submitted: Symp. on *Ceramic Matrix Composites*, 92nd Annual Mtg. of the Amer. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Flexure and Compressive Deformation of SiC-Whisker Reinforced Alumina

A. R. de Arellano-Lopez (Universidad de Sevilla, Spain), A. Domínguez-Rodríguez (U. de Sevilla), H.-T Lin (Oak Ridge National Laboratory), P. F. Becher, (ORNL), K. C. Goretti, and J. L. Routbort (MSD)

INVITED TALK to be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc., Symp. on *Ceramic Matrix Composites*, Cincinnati, OH, April 28-May 2, 1991.

Electrode Development in Monolithic Solid Oxide Fuel Cells

D. W. Dees (CMT), U. Balachandran, S. E. Dorris, J. J. Heiberger (CMT), C. C. McPheeters (CMT), and J. J. Picciolo

To be published in Proc. AIChE Ann. Mtg., San Francisco, CA, November 5-10, 1989.

Processing and Fabrication of $YBa_2Cu_3O_x/Ag$ Composite Wires and Coils

D. Divecha, (Naval Surface Warfare Center), W. A. Ferrando (NSWC), U. Balachandran, J. T. Dusek, J. J. Picciolo, J. P. Singh, and R. B. Poeppel

To be presented at 2nd Intl. *Ceramic Science and Technology* Congress and The American Ceramic Society's *Electronics Div. Mtg.*, Orlando, FL, Nov. 12-15, 1990.

Creep and Diffusion in Nonstoichiometric Oxides

A. Domínguez-Rodríguez (Universidad de Sevilla), J. Castaing (LPM, CNRS), K. C. Goretti, and J. L. Routbort (MSD)

To be presented at Symp on *Point Defects Relative Properties of Ceramics*, 93rd Ann. Mtg. of Am. Ceram. Soc. Symp. on *Point Defects Related Properties of Ceramics*, Cincinnati, OH, Apr. 28-May 3, 1991.

Y₂BaCuO₅ as a Substrate for YBa₂Cu₃O_x

S. E. Dorris, M. T. Lanagan, D. M. Moffatt (Pennsylvania State University), H. J. Leu, C. A. Youngdahl, U. Balachandran, A. Cazzato, D. E. Bloomberg, and K. C. Goretti
Jpn. J. Appl. Phys. 28(8), L 1415-L 1416 (August 1989).

Fabrication of Superconductor Coils

S. E. Dorris, H. J. Leu, J. P. Singh, A. Cazzato, and R. B. Poeppel
 Presented at 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 156.

Processing YBa₂Cu₃O_x Wires in O₃/O₂

S. E. Dorris, K. C. Goretti, U. Balachandran, J. T. Dusek, D. Shi (MSD), and R. B. Poeppel
 Presented at 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 145.

Fabrication of Superconductor Coils

S. E. Dorris, J. T. Dusek, J. J. Picciolo, H. J. Leu, J. P. Singh, A. Cazzato, and R. B. Poeppel
 To be published in Proc. First Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989.

Processing YBa₂Cu₃O_x Wires in O₃/O₂

S. E. Dorris, K. C. Goretti, U. Balachandran, J. T. Dusek, D. Shi, and R. B. Poeppel
 To be published in Proc. 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989.

YBa₂Cu₃O_x Superconductor Coil: Processing and Properties

S. E. Dorris, J. T. Dusek, J. J. Picciolo, R. A. Russell, J. P. Singh, and R. B. Poeppel
 INVITED PAPER: Proc. Intl. Conf. on *Electrical Machines*, Cambridge, MA, Aug. 13-15, 1990, pp. 7-12.

Control of YBa₂Cu₃O_{7-x} Degradation during Heat Treatment

S. E. Dorris, R. B. Poeppel, J. J. Picciolo, U. Balachandran, M. T. Lanagan, C. Z. Zhang, K. Merkle (MSD), Y. Gao (MSD), J. T. Dusek, J. E. Jordan (Reliance Electric), R. F. Schiferl (Rel. Elec.), and J. D. Edick (Rel. Elec.)
 To be presented in Proc. 2nd World Congress on *Superconductivity*, Houston, TX, Sept. 10-13, 1990.

Atmosphere Control during Fabrication of Multilayer Superconductor Coils

S. E. Dorris, U. Balachandran, M. T. Lanagan, J. T. Dusek, J. J. Picciolo, K. L. Merkle (MSD), Y. Gao (MSD), and R. B. Poeppel
 To be presented at 93rd Ann. Mtg., of the Am. Ceram. Soc.

Bismuth-Based Superconductors Prepared by a Solution Technique

D. I. Dos Santos (University of Sao Paulo), U. Balachandran, R. A. Guttschow, and R. B. Poeppel
 Submitted to *J. Non-Crystalline Solids*.

Development of Nondestructive Evaluation Methods for Structural Ceramics

W. A. Ellingson, R. A. Roberts, N. Gopalsami, S. L. Dieckman, J. P. Singh, and J. J. Vaitekunas

Presented at 3rd Ann. *Fossil Energy Materials Program Contractors' Conf.*, Oak Ridge, TN, August 8-10, 1989; abstract in Program and Abstracts booklet, p. 47.

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, R. A. Roberts, J. P. Singh, C. Y. Chu, N. Gopalsami, S. L. Dieckman, T. Hentea (Purdue U.), and J. J. Vaitekunas

Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending March 31, 1989, ORNL/FMP-89/1 (July 1989), pp. 11-33.

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, C. Y. Chu, N. Gopalsami, S. L. Dieckman, T. Hentea (Purdue University), K. Gopalan, J. J. Vaitekunas

Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending September 30, 1989, ORNL/FMP-89/2, (January 1990) pp. 11-35.

Development of Nondestructive Evaluation Methods for Predicting Effects of Flaws on Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, C. Y. Chu, T. Hentea, and P. Rizo

Presented at 4th Ann. Conf. on *Fossil Energy Materials*, Oak Ridge, TN, May 15-17, 1990, abstract in Conf. Abstracts booklet, p. 25.

Development of Nondestructive Evaluation Methods for Predicting Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, E.-Y Chu, T. Hentea (Purdue University-Calumet), and P. Rizo (Visiting Sci., CEA/Leti, Grenoble, France)

To be published in Proc. 4th Ann. Conf. on *Fossil Energy Materials* Oak Ridge, TN, May 15-17, 1990.

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, C-Y Chu, N. Gopalsami, S. H. Sheen, S. L. Dieckman, T. Luethi (EMPA Laboratories), W. P. Lawrence, and T. Hentea (Purdue University-Calumet)

Fossil Energy Materials Program, Semiannual Progress Report for the Period Ending Sept. 30, 1990.

Corrosion and Mechanical Properties of Alloys in FBC and Mixed-Gas Environments

W. A. Ellingson, J. P. Singh, C-Y. Chu, N. Gopalsami, S. H. Sheen, S. L. Dieckman, T. Luethi (EMPA Laboratories), W. P. Lawrence, and T. Hentea (Purdue University-Calumet)

Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending September 30, 1990, in press.

J_c Degradation of YBa₂Cu₃O_{7-x} Superconductors Sintered in CO₂/O₂

Y. Gao, Y. Li, K. L. Merkle, J. N. Mundy, C. Zhang (MCT), U. Balachandran (MCT) and R. B. Poeppel (MCT).

Submitted: Spring MRS Mtg., San Francisco, CA, April 16-21, 1990.

Decomposition of YBa₂Cu₃O_{7-x} during Annealing in CO₂/O₂ Mixtures

Y. Gao (MSD), K. L. Merkle (MSD), C. Zhang, U. Balachandran, and R. B. Poeppel

Submitted to J. Mater. Res..

J_c Degradation of YBa₂Cu₃O_{7-x} Superconductors Sintered in CO₂/O₂

Y. Gao, Y. Li, K. L. Merkle, J. N. Mundy, C. Zhang, U. Balachandran, and R. B. Poeppel

Submitted to Materials Letters 9 (10), pp. 347-352.

Decomposition of YBa₂Cu₃O_{7-x} during Annealing in CO₂/O₂

Y. Gao (MSD), K. L. Merkle (MSD), C. Zhang, U. Balachandran, and R. B. Poeppel

J. Mater. Res., 5, (7), pp. 1363-1367 (July 1990).

Texturing of RBa₂Cu₃O_{7-x} Superconductors

K. C. Goretta, A. J. Schultz, D. W. Capone (Supercon, Inc.), T. L. Tolt (Case Western Reserve University), U. Balachandran, J. T. Dusek, M. T. Lanagan, R. B. Poeppel, J. P. Singh, D. Shi, R. L. McDaniel, D. S. Applegate, J. K. Degener, and J. S. Kallend (Illinois Institute of Technology)

Research Update, 1988, Ceramic Superconductors II, ed. Man F. Yan (Proc. 90th Ann. Mtg. of Am. Ceram. Soc. *Ceramic Superconductors Symp.*, Cincinnati, OH, May 1-5, 1988), The American Ceramic Society, Inc., Westerville, OH, 1988, pp. 323-331.

BOOK REVIEW: *Strengthening of Ceramics: Treatments, Tests, and Design Applications* by Henry P. Kirchner (Marcel Dekker, New York, 1979)

K. C. Goretta

INVITED REVIEW: *Adv. Mater. Manuf. Processes* 4(1), 156-158 (1989).

Synthesis and Sintering of Tl₂Ca₂Ba₂Cu₃O_x

K. C. Goretta, D. Shi, B. S. Malecki, M. C. Hash (CMT), and I. Bloom (CMT)

Supercond. Sci. Technol. 2, 192-194 (1989).

YBa₂Cu₃O_x Toughened by ZrO₂ Additions

K. C. Goretta, O. D. Lacy, U. Balachandran, D. Shi, and J. L. Routbort (MSD)

J. Mater. Sci. Lett. 9, 30-381 (1990).

Hyper- and Hypobaric Processing of Tl-Ba-Ca-Cu-O Superconductors

K. C. Goretta, J. L. Routbort (MSD), D. Shi (MSD), J. G. Chen, M. Xu, and M. C. Hash (CMT)

INVITED PAPER: Submitted to the Fall Mtg. of the Material Research Soc., Boston, MA, November 27-December 2, 1989.

Diffusion and Processing of $\text{YBa}_2\text{Cu}_3\text{O}_x$

K. C. Goretta, R. B. Poeppel, D. Shi, N. Chen, S. J. Rothman, and J. L. Routbort
Ceram. Trans. 13, pp. 369-379 (1990). (Proc. 1st Intl. *Ceram. Science and Technology* Congress, Anaheim, CA, October 31-November 3, 1989.)

Synthesis of Tl-Ca-Ba-Cu-O Superconductors

K. C. Goretta, J. G. Chen (MSD), N. Chen (MSD), M. C. Hash (CMT), and D. Shi (MSD)
 Submitted to *Mater. Res. Bul.*

Toughened $\text{YBa}_2\text{Cu}_3\text{O}_x/\text{ZrO}_2$ Composites

K. C. Goretta, M. Kullberg, O. D. Lacy, U. Balachandran, R. B. Poeppel, D. Shi, M. Xu, and J. L. Routbort
 Presented at the 1990 TMS Ann. Mtg. Exhibition, Anaheim, CA, February 19-21, 1990.

Deformation Processing of $\text{YBa}_2\text{Cu}_3\text{O}_x$

K. C. Goretta, A. Brandstädter, J. P. Singh, R. B. Poeppel, A. J. Schultz, D. Shi, and J. L. Routbort
 Presented at the 1990 TMS Ann. Mtg. Exhibition, Anaheim, CA, February 19-21, 1990.

Processing Thallium-Based Superconductors

K. C. Goretta, M. T. Lanagan, J. R. Hull, J. L. Routbort, D. L. Shi, N. Chen, and M. C. Hash (CMT)
 To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

High-Temperature Mechanical Behavior of Porous Open-cell Al_2O_3

K. C. Goretta, R. Brezny (Pennsylvania State University), C. Q. Dam (Penn. State U.), D. J. Green (Penn. State U.), A. R. de Arellano-Lopez (Universidad de Sevilla, Spain), and A. Dominguez-Rodriguez (U. de Sevilla)
Mater. Sci. Eng. A124, 151-158 (1990).

Creep of Pure and Doped $\text{YBa}_2\text{Cu}_3\text{O}_x$

K. C. Goretta, A. C. Blondo, S. E. Dorris, and J. L. Routbort
 To be presented at 1990 *Mater. Research Society Fall Mtg.*, Symp. H: *Issues in Application of Ceramic Superconductors*, Boston, MA, Nov. 26-Dec 1, 1990.

Texture Analysis of Bulk $\text{YBa}_2\text{Cu}_3\text{O}_x$ by Neutron Diffraction

K. G. Goretta, A. C. Blondo, A. J. Schultz (CHM), and J. S. Kallend (Illinois Institute of Technology)
 To be presented at World Congress on *Superconductivity*, Houston, TX, Sept. 9-13, 1990.

Solid-Particle Erosion of Aluminum/Particulate Ceramic Composites

K. C. Goretta, W. Wu, J. L. Routborg (MSD), and P. K. Rohatgi (University of Wisconsin-Milwaukee)

Tribology of Composite Materials (Proc. ASM Conf. on *Tribology of Composite Mater.*, Oak Ridge, TN, May 1-3, 1990), ASM International, Materials Park, OH, 1990, pp. 147-155.

Sintering and Creep of $\text{YBa}_2\text{Cu}_3\text{O}_x$ and Y_2BaCuO_y

K. C. Goretta, A. C. Blondo, S. E. Dorris, N. Chen (MSD), J. L. Routbort (MSD), A. R. de Arellano-Lopez (Universidad de Sevilla, Spain), and A. Domínguez-Rodríguez (U. de Sevilla)

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc.

Compressive Creep of $\text{YBa}_2\text{Cu}_3\text{O}_x$

K. C. Goretta, J. L. Routbort, A. C. Blondo, Y. Gao, A. R. de Arellano-Lopez (Universidad de Sevilla, Spain), and A. Domínguez-Rodríguez (U. de Sevilla)

J. Mater. Res. 5 (12) pp. 2766-2770 (December 1990)

Toughened $\text{YBa}_2\text{Cu}_{1-x}\text{O}_x/\text{ZrO}_2$ Composites

K. C. Goretta, M. Kullberg, D. Bar (MSD), S. E. Dorris, U. Balachandran, D. Shi (MSD), R. B. Poeppel, and J. L. Routbort (MSD)

High Temperature Superconducting Compounds II, ed. S. H. Whang, A. DasGupta, and R. Laibowitz, (Proc. 1990 TMS Symp. on High Temperature Superconducting Compounds, Anaheim, CA, February 19-21, 1990), The Minerals, Metals and Materials Society, Warrendale, PA, 1990, pp. 193-203.

Deformation Processing of $\text{YBa}_2\text{Cu}_3\text{O}_x$

K. C. Goretta, M. J. McGuire, A. Brandstadter, J. P. Singh, R. B. Poeppel, A. J. Schultz (CHM), and J. L. Routbort (MSD)

High Temperature Superconducting Compounds II, ed. S. H. Whang, A. DasGupta, and R. Laibowitz, (Proc. 1990 TMS Symp. on High Temperature Superconducting Compounds, Anaheim, CA, February 19-21, 1990), The Minerals, Metals and Materials Society, Warrendale, PA, 1990, pp. 263-274.

Use of 96Sn-4Ag Alloy as the Binder for Carbon Fiber-Reinforced Superconductor

C. T. Ho (State University of New York at Buffalo), D. D. L. Chung (SUNY at Buffalo), U. Balachandran

To be presented at 4th Ann. Conf. on *Superconductivity and Applications*, Buffalo, NY. Sept. 18-20, 1990.

Heat Transfer Issues in the Fabrication and Operation of Ceramic Superconductors

J. R. Hull, T. M. Kuzay, and R. B. Poeppel

INVITED PAPER to be presented at American Society of Mechanical Engineers Winter Ann. Mtg., Dallas, TX, Nov. 25-30, 1990.

Microwave Heating of Grain Boundaries in Ceramics

D. L. Johnson (Visiting faculty, Northwestern University)

Submitted to J. Amer. Ceram. Soc.

Texture Analysis of Bulk $\text{YBa}_2\text{Cu}_3\text{O}_x$ by Neutron Diffraction

J. S. Kallend (Illinois Institute of Technology), A. C. Blondo, A. J. Schultz (CHM), and K. C. Goretta

To be published in *Proc. Second World Congress on Superconductivity*, Houston, TX, Sept. 10-13, 1990.

Synthesis of 85 K Bi-Sr-Ca-Cu-O Superconductor

F. A. Karbarz, O. D. Lacy, K. C. Goretta, U. Balachandran, D. Shi, J. G. Chen, M. Xu, and M. C. Hash

Mater. Res. Bull. 25, 251-256 (1990).

The Effects of the Solution Structure on the Microstructure and Properties of Sinter Forged Sol-Gel-Derived Superconductors

D. Kenzer (University of Illinois at Urbana-Champaign), M. Teepe (UIUC), G. Moore (UIUC), G. Kordas (UIUC), M. E. Biznek, U. Balachandran, M. L. Kullberg, R. B. Poeppel, Y. L. Jeng (Northwestern University), and D. L. Johnson (NU).

To be presented at Symp. M on *High-Temperature Superconductors: Fundamental Properties and Novel Materials Process*, Fall Mtg. of the Materials Research Society, Boston, MA, November 27-December 2, 1989.

Processing and Properties of Zn-Ni-Ti-O PTCR Thermistors

K. S. Kirkpatrick, U. Balachandran, R. B. Poeppel, and T. O. Mason (Northwestern University)

To be presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc.

Impedance Spectra and Microscopy during Processing Reactions of Zinc Oxide Varistors

K. S. Kirkpatrick, U. Balachandran, R. B. Poeppel, and T. O. Mason (Northwestern University)

To be presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc.

A Sol-Gel Method for Preparing Oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$

M. L. Mullberg (Amoco Chemical Co.), M. T. Lanagan, J. M. Turk, W. Wu, and R. B. Poeppel

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

A Sol-gel Method for Preparing Oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Films on Silver Substrates

M. L. Kullberg (Amoco Chemical Co.), M. T. Lanagan, W. Wu, and R. B. Poeppel
Submitted to *J. of Mater. Res.*

Neutron Diffraction NDE for Advanced Composites

D. S. Kupperman, S. Majumdar, and J. P. Singh

Trans. ASME 112, 198-201 (April 1990).

Application of Neutron Diffraction to the Characterization of Residual Thermal Strains in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}/\text{Ag}$

D. S. Kupperman, J. P. Singh, J. Faber, Jr., and R. L. Hitterman

J. Appl. Phys. 66(7), 3396-3398 (October 1, 1989).

Use of Neutron Diffraction in Determining Strains in High-Temperature Superconducting Composites

D. S. Kupperman, J. P. Singh, J. Faber, Jr., and R. L. Hitterman

Presented at 1989 Fall Materials Research Soc. Mtg., Boston, MA, November 27-December 2, 1989, abstract in Final Program and Abstracts booklet, p. 335.

Application of Neutron Diffraction NDE to High-Temperature Superconducting Composites

D. S. Kupperman, S. P. Singh, S. Majumdar, A. C. Raptis, and R. L. Hitterman (MSD)

To be published in *Review of Progress in Quantitative NDE*, Brunswick, ME, July 23-28, 1989.

Use of Neutron Diffraction in Determining Strains in High-Temperature Superconducting Composites

D. S. Kupperman, J. P. Singh, S. Majumdar, R. L. Hitterman (MSD), and J. Faber, Jr. (Amoco Research).

Proc. 1989 Fall Materials Research Society Symp., Boston, MA, Vol 166, pp. 195-201 (1990).

Production of Wires and Coils from High-Temperature Superconducting Materials

M. T. Lanagan, U. Balachandran, S. E. Dorris, J. T. Dusek, K. C. Goretta, R. B. Poeppel, J. P. Singh, and C. A. Youngdahl

Presented at Workshop on *High-T_c Superconductivity*, Huntsville, AL, May 23-25, 1989, abstract in Program & Technical Paper Abstracts booklet, p. 48.

BOOK REVIEW: *Ceramic Materials for Electronics: Properties and Applications*, edited by Relva C. Buchanan (Marcel Dekker, New York, 1986)

M. T. Lanagan

INVITED REVIEW: *Adv. Mater. Manuf. Processes* 4(3), 449-450 (1989).

Production of Wires and Coils from High-Temperature Superconducting Materials

M. T. Lanagan, U. Balachandran, M. T. Cao, S. E. Dorris, J. T. Dusek, K. C. Goretta, R. B. Poeppel, J. P. Singh, and C. A. Youngdahl

Proc. Workshop on *High-T_c Superconductivity*, Huntsville, AL, May 23-25, 1989, Guidance & Control Information Analysis Center (GACIAC), IIT Research Institute, Huntsville, AL, 1989, GACIAC PR-89-02, pp. 307-310.

The Effect of Magnetic Field on the Critical Current Density of Bulk Superconducting Wires

M. T. Lanagan, U. Balachandran, C. A. Youngdahl, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel

Presented at the Fall Mtg. of the Materials Research Soc., Boston, MA, November 27-December 2, 1989.

RF Surface Resistance Measurements in the Pb-Bi-Sr-Ca-Cu-O System

M. T. Lanagan, C. T. Bohn (EP), J. R. Delayen (EP), M. C. Einloth, R. N. Vogt, and U. Balachandran

Presented at the Fall Mtg. of the Material Research Soc., Boston, MA, November 27-December 2, 1989.

Processing and Characterization of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Thick Films

M. T. Lanagan, S. E. Dorris, J. P. Singh, J. M. Turk, J. J. Picciolo, R. B. Poeppel, M. J. McGuire (University of Illinois at Chicago), W. Wu, and S. Danyluk (UIC).

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Effect of Magnetic Field on the Critical Current Density of Bulk Superconducting Wires

M. T. Lanagan, U. Balachandran, C. A. Youngdahl, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel

To be published in Proc. Fall Mtg. of the Materials Research Soc., Boston, MA, November 27-December 2, 1989.

RF Surface Resistance Measurements in the Pb-Bi-Sr-Ca-Cu-O System

M. T. Lanagan, C. T. Bohn (EP), J. R. Delayen (EP), M. C. Einloth, R. N. Vogt, and U. Balachandran

To be published in Proc. Fall Mtg. of the Material Research Soc., Boston, MA, November 27-December 2, 1989.

Fabrication of Multilayer Superconductor Coils

M. T. Lanagan, S. E. Dorris, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Electrical Properties of High-Temperature Superconductors at Microwave Frequencies

M. T. Lanagan, C. L. Bohn (EP), J. R. Delayen (EP), and R. B. Poeppel

Presented at 7th Intl. Symp. on *Applications of Ferroelectrics*, Champaign, IL, June 6-8, 1990, abstract in Book of Abstracts, p. 3.1.

Fabrication and Potential Applications of Polycrystalline High-Temperature Superconductors

M. T. Lanagan, S. E. Dorris, J. P. Singh, K. C. Goretta, U. Balachandran, C. A. Youngdahl, J. T. Dusek, J. J. Picciolo, and R. B. Poeppel

Submitted to J. Metals.

Processing and Characterization of High-Temperature Superconducting Thick Films

M. T. Lanagan, S. E. Dorris, R. B. Poeppel, M. J. McGuire (University of Illinois at Chicago), W. Wu (UIC), and S. Danyluk (UIC)

INVITED PAPER: Hybrid Circuit Technol., 37-40 (August 1990).

Microstructure and Electronic Properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Sol-Gel Films

M. T. Lanagan (EP), B. Prorok, J. R. Delayen (EP), C. L. Bohn (EP), C. Roche (EP), R. Poeppel, W. Wu (University of Illinois at Chicago), S. Danyluk (UIC), and M. Kullberg (Amoco Chemical Co.).

To be presented at *Materials Research Society*, Fall Mtg., Boston, MA, Dec 2-7, 1990.

Processing and Microwave Electrical Properties of High-Temperature Superconductors

M. T. Lanagan and R. B. Poeppel

To be presented at Intl. Symp. on *Applications of Ferroelectrics*, Champaign, IL, June 6-8, 1990.

Sputter Deposition of BSCCO Films from a Hollow Cathode

M. T. Lanagan, R. T. Kampwirth (MSD), R. J. Doyle (MSD), S. M. Kowalski, D. J. Miller (MSD), and K. E. Gray (MSD)

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc., Cincinnati, OH, Apr. 28-May 1, 1991.

Preparation and Properties of Y-124 Superconductor Made by a Chemical Precipitation Method

H. L. Laquer (CryoPower Associates), J. R. Gaines, Jr. (Superconductive Components, Inc.), S. Brainard (SCI), S. D. Hutson (SCI), J. Pisanelli (SCI), D. W. Cooke (Los Alamos National Laboratory), E. R. Gray (LANL), K. C. Ott (LANL), E. J. Peterson (LANL), J. S. Smith (LANL), U. Balachandran, M. T. Lanagan, R. B. Poeppel, J. D. Wolf (University of Dayton Research Institute), and F. C. Laquer (University of Nebraska).

To be published in Proc. 1990 Superconductivity Conf., Snowmass, CO, Sept. 24-28, 1990.

Fabrication of a Superconducting Coil for Solenoid Applications

H. J. Leu, J. P. Singh, S. E. Dorris, and R. B. Poeppel

Submitted to Supercond. Sci. Technol.

Mechanical Properties of CuO

J. K. Lumpp, N. Chen, K. C. Goretta, and H. M. Hero (Nalco Chemical Co.)

J. High Temperature Materials and Processes, 9, (1), 1990.

Solid-Particle Erosion of a Graphite-Fiber-Reinforced BMI Polymer Composite

P. J. Mathias, W. Wu, K. C. Goretta, J. L. Routbort, D. P. Groppi (Allied Signal, Inc., DesPlaines, IL) and K. R. Karasek (Allied Signal, Inc.)

Wear 135, 162-169 (July 24, 1989).

Solid Particle Erosion of a Graphite-Fiber Reinforced Bismaleimide Polymer Composite

P. J. Mathias, W. Wu, K. C. Goretta, J. L. Routbort (MSD), D. P. Groppi (Allied Signal, Inc.), and K. R. Karasek (Allied Signal, Inc.)

Wear 135, 161-169 (1989).

Thermomechanical Processing of YBCO-Ag Sheathed Wires

M. McGuire (University of Illinois at Chicago), S. Danyluk (UIC), K. C. Goretta, M. T. Lanagan, U. Balachandran, and R. B. Poeppel

To be presented at 2nd Intl. *Ceramic Science and Technology* Congress and The American Ceramic Society's *Electronics Div. Mtg.*, Orlando, FL, Nov. 12-15, 1990.

The Effect of Composition and Processing on High-T_c Superconductors Containing Bismuth

A. S. Nash (Marquette University) and R. B. Poeppel

Presented at 1989 *Powder Metallurgy* Conf. and Exhibition, San Diego, CA, June 11-14, 1989.

The Effect of Composition and Processing on High T_c Superconductors Containing Bismuth

A. S. Nash (Marquette University), K. C. Goretta, and R. B. Poeppel

Advances in Powder Metallurgy, (Proc. 1989 Powder Metallurgy Conf. and Exhibition, San Diego, CA, June 11-14, 1989), Metal Powder Industries Federation, Princeton, NJ, 1989, Vol. 2, pp. 517-530.

Hot Isostatic Pressing of Pure and Ag-Doped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$

A. S. Nash (Marquette Univ.), P. Nash (Illinois Institute of Technology), R. B. Poeppel, and K. C. Goretta

To be presented at 1990 Materials Research Society Fall Mtg., Boston, MA, Nov. 26-Dec. 1, 1990.

Bi-Sr-Ca-Cu-O/ Ca_2CuO_3 Composites

J. M. Phillips, S. Krause, M. T. Lanagan, R. A. Olson, P. R. Sharpe, M. L. Ray, S. E. Dorris, and K. C. Goretta

Submitted to Mater. Lett.

Improved Processing of Ceramic Superconductors

R. B. Poeppel, U. Balachandran, J. E. Emerson, S. A. Johnson (CMT), M. T. Lanagan, C. A. Youngdahl, and N. G. Eror (Oregon Graduate Center)

Presented at 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 141.

Diffusion and Processing of $\text{YBa}_2\text{Cu}_3\text{O}_x$

R. B. Poeppel, K. C. Goretta, D. Shi, N. Chen, S. J. Rothman, and J. L. Routhort

Presented at 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 144.

Fabrication and Wire Extrusion of Ceramic Superconductors

R. B. Poeppel, U. Balachandran, J. P. Singh, J. T. Dusek, J. J. Picciolo, S. E. Dorris, M. T. Lanagan, K. C. Goretta, and C. A. Youngdahl

Presented at the 2nd Topical Conf. on *Emerging Technologies in Materials*, San Francisco, CA, November 6-9, 1989.

Improved Processing of Ceramic Superconductors

R. B. Poeppel, U. Balachandran, J. E. Emerson, S. A. Johnson (CMT), M. T. Lanagan, C. A. Youngdahl, and N. G. Eror (University of Pittsburgh)

To be published in Proc. 1st Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989.

Fabrication Advances for Improved Performance of Long Lengths of High-Temperature Superconducting Wire and Tape.

R. B. Poeppel, J. R. Hull, U. Balachandran, S. E. Dorris, J. T. Dusek, K. C. Goretta, M. T. Lanagan, J. J. Picciolo, and J. P. Singh

To be presented at 1990 Superconductivity Conf., Aspen, CO., Sept. 24-28, 1990.

Characterization of YBCO Superconductor Sintered in CO₂-Containing Atmosphere

R. B. Poeppel, U. Balachandran, C. Zhang, Y. Gao (MSD), Y. Li (MSD), K. L. Merkle (MSD), B. W. Veal (MSD), and H. Shi (MSD)

To be presented at 2nd Intl. Ceram. Sci. and Techn. Congress, and the American Society Electronic Div. Mtg., Orlando, FL, Nov. 12-15, 1990.

Practical Superconductor Development for Electrical Power Applications, Semiannual Report -- October 1989-June 1990

R. B. Poeppel, coordinator, K. C. Goretti, compiler
ANL-90/25 (June 1990).

Atmosphere Control during Preparation of YBa₂Cu₃O_{7-x}

R. B. Poeppel, S. E. Dorris, J. J. Picciolo, U. Balachandran, M. T. Lanagan, C. Z. Zhang, K. Merkle (MSD), Y. Gao (MSD), and J. T. Dusek

To be presented at 3rd Intl. Symp. on *Superconductivity*, Sendai, Miyagi Prefecture, Japan, November 6-9, 1990.

Atmosphere Control during Preparation of YBa₂Cu₃O_{7-x} Magnet Windings

R. B. Poeppel, S. E. Dorris, J. J. Picciolo, U. Balachandran, M. T. Lanagan, C. Z. Zhang, K. Merkle (MSD), Y. Gao (MSD), and J. T. Dusek

To be published in Proc. 3rd Intl. Symp. on *Superconductivity*, Sendai, Miyagi Prefecture, Japan, Nov. 6-9, 1990.

Steady-State Deformation of Some Lithium Ceramics

R. B. Poeppel, M. C. Billone, D. S. Applegate, E. Buchmann, B. Lonschien, and J. L. Routbort

Advances in Ceramics 25, 175-181, American Ceramic Society, Inc., *Fabrication and Properties of Lithium Ceramics*.

Kinetics of Recrystallization and Fission-Gas Induced Swelling in High-Burnup UO₂ and U₃Si₂ Nuclear Fuels

J. Rest and G. L. Hofman

INVITED PAPER to be published in Proc. NATO Advanced Research Workshop on *Fundamental Aspects of Inert Gases in Solids*, Bonas, France, Sept. 16-22, 1990.

Texture Melting of the 2212 Phase of Bi-Sr-Ca-Cu Oxides

G. A. Risch (U. of Cincinnati), M. T. Lanagan, K. C. Goretti, and R. B. Poeppel

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc., Cincinnati, OH, Apr. 28-May 2, 1991.

Microstructure and Properties of Alumina-Whisker-Reinforced Tetragonal Zirconia Polycrystal Matrix Composites

J. M. Roberts, J. P. Singh, and R. O. Scattergood

To be presented at 15th Ann. Conf. on *Composites and Advanced Ceramics*, Cocoa Beach, FL, Jan. 13-16, 1991.

Oxygen Diffusion in High- T_c Superconductors

S. J. Rothman, J. L. Routbort, L. J. Nowicki, K. C. Goretta, L. J. Thompson, J. N. Mundy, and J. E. Baker (University of Illinois at Urbana-Champaign)

INVITED PAPER: Defect and Diffusion Forum 66-69, 1081-1096 (1989). (Proc. Intl. Conf. on *Diffusion in Metals and Alloys*, Balatonfüred, Hungary, September 5-9, 1988.)

SIMS Measurement of Oxygen Tracer Diffusion in $YBa_2Cu_3O_{7-\delta}$

S. J. Rothman, J. L. Routbort, J. E. Baker (University of Illinois at Urbana-Champaign), L. J. Nowicki, K. C. Goretta, L. J. Thompson, and J. N. Mundy

INVITED PAPER: Minerals, Metals and Materials Soc., pp. 289-305 (1989), ed. A. D. Romig, Jr. and M. A. Dayananda (Proc. Symp. on *Diffusion Analysis and Applications*, AIME Fall Mtg., Chicago, IL, September 25-29, 1988).

Erosion of Ceramic Matrix Whisker Reinforced Composites

J. L. Routbort, D. A. Helberg, and K. C. Goretta

Submitted for the session on *Tribology* to be held as a joint session of the Basic Science Div. and the Engineering Ceramics Div. at the *92nd Annual Mtg. of the Am. Ceram. Soc.*, Dallas, TX, April 22-26, 1990.

Erosion of Ceramic Matrix Composites

J. L. Routbort, D. A. Helberg, and K. C. Goretta

INVITED PAPER to be published in the Inaugural Issue of *J. Hard Mater.*

Cation and Anion Tracer Diffusion in $YBa_2Cu_3O_{7-\delta}$

J. L. Routbort, N. Chen, K. C. Goretta, and S. J. Rothman

INVITED KEYNOTE LECTURE to be presented at the ICMC '90 Topical Conf. *High-Temperature Superconductors, Materials Aspects*, Garmisch-Partenkirchen, West Germany, May 9-11, 1990.

Erosion of Ceramic Composites by Various Erodents

J. L. Routbort, C.-Y. Chu, J. M. Roberts, J. P. Singh, W. Wu, and K. C. Goretta

Submitted: 4th Berkeley Conf on *Corrosion-Erosion-Wear of Materials at Elevated Temperatures*, Berkeley, CA, January 31- February 2, 1990.

Fracture Toughness and Solid Particle Erosion of Ceramic-Matrix Whisker-Reinforced Composites

J. L. Routbort, K. C. Goretta, C. -Y Chu, and J. P. Singh

Tribology of Composite Materials (Proc. ASM Conf. on *Tribology of Composite Mater.*, Oak Ridge, TN, May 1-3, 1990, ASM International, Materials Park, OH, 1990, pp. 355-360.

Solid Particle Erosion of Crystalline $Ni_{80}P_{20}$

R. B. Schwarz (Los Alamos National Laboratory), T. J. Tien (LANL), A. Mayer (LANL), T. S. Lee (MSD), K. C. Goretta, and J. L. Routbort (MSD)

Submitted to *Wear*.

Structural and Superconducting Properties of Oxygen-Deficient $\text{NdBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductors

H. Shaked (Nuclear Research Center-Negev), B. W. Veal, J. Faber, Jr., R. L. Hitterman, U. Balachandran, G. Tomlins, H. Shi, L. Morss, and A. P. Paulikas
Phys. Rev. B. 41(7), 4173-4180 (1 March 1990).

Transport Critical Current Behavior and Grain Boundary Microstructure in $\text{YBa}_2\text{Cu}_3\text{O}_x$

D. Shi, J. G. Chen (University of Illinois at Urbana-Champaign), M. Xu (Georgia Institute of Technology), A. L. Cornelius (Ohio State University), U. Balachandran, and K. C. Goretta

Submitted to Superconductor Science Technology 3, pp. 222 - 226.

A Superconducting Coil Made of Filamentary Composites

D. Shi, M. Xu (Georgia Institute of Technology), J. G. Chen (University of Illinois at Urbana-Champaign), S. G. Lanan (De Vry Institute of Technology), D. Miller, and K. C. Goretta

Mater. Lett. 9(1), 1-4 (December 1989).

Transport Critical Current Density and Microstructure in Extruded $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Wires Processed by Zone Melting

D. Shi, H. Krishnan, J. M. Hong, P. J. McGinn (University of Notre Dame), M. Xu, J. G. Chen (University of Illinois at Urbana-Champaign), M. M. Fang (Western Illinois University), U. Welp, M. T. Lanagan, K. C. Goretta, J. T. Dusek, J. J. Picciolo, and U. Balachandran

Submitted to J. Appl. Phys.

Transport Current Properties and Microstructures in Zone Melted $\text{YBa}_2\text{Cu}_3\text{O}_x$ Wires

D. Shi, M. Xu, J. G. Chen, M. M. Fang, H. Kishnan, J. M. Hong, U. Welp, P. J. McGinn, W. H. Chen, M. T. Lanagan, K. C. Goretta, J. T. Dusek, J. J. Picciolo, and U. Balachandran

Submitted to 1990 Spring Meeting of the Materials Research Society, *Symposium D: Critical Currents in High Temperature Superconductors*, San Francisco, CA, April 16-21, 1990.

Effect of Silver and Silver Oxide Additions on the Mechanical and Superconducting Properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductors

J. P. Singh, H. J. Leu, R. B. Poeppel, E. Van Voorhees, G. T. Goudey, K. Winsley, and D. Shi

J. Appl. Phys. 66(7), 3154-3159 (1 October 1989).

Effects of Flaws on the Fracture Behavior of Structural Ceramics

J. P. Singh, C. Y. Chu, R. A. Roberts, W. A. Ellingson, and A. L. Bosak

INVITED TALK presented at Third Ann. *Fossil Energy Materials Program Contractors' Conf.*, Oak Ridge, TN, August 8-10, 1989; abstract in Program and Abstracts booklet, pp. 23-24.

Fracture Behavior and Nondestructive Evaluation of Si_3N_4 and Its Composites

J. P. Singh, C. Y. Chu, A. Wagh (University of West Indies), R. A. Roberts (Ames Laboratory), and W. A. Ellingson

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Fabrication of Silver-Based Superconducting Coil for Solenoid Application

J. P. Singh, H. J. Leu, S. E. Dorris, and R. B. Poeppel

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, and R. L. Hitterman

To be presented at the Intl. Conf. on *Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, R. L. Hitterman (MSD), and D. W. Schroeder
 INVITED PAPER to be published in Proc. Intl. Conf. on *Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

$\text{YBa}_2\text{Cu}_3\text{O}_x$ Composites with Improved Toughness and Strength

J. P. Singh, H. J. Leu (Science and Technology Center for Superconductivity), M. L. Kullberg, R. B. Poeppel, and K. C. Goretti

To be presented at ASME Winter Annual Mtg., Dallas, TX, Nov. 25-30, 1990.

$\text{YBa}_2\text{Cu}_3\text{O}_x$ Composites with Improved Toughness and Strength

J. P. Singh, H. J. Leu (Science and Technology Center for Superconductivity), M. L. Kullberg, R. B. Poeppel, and K. C. Goretti

To be published in Proc. ASME Winter Annual Mtg, Dallas, TX, Nov. 25-30, 1990.

Strength/Grain-Size Relationships and Internal Stresses in YBCO Superconductors

J. P. Singh, R. Guttschow, D. S. Kupperman, J. T. Dusek, and R. B. Poeppel

To be presented at 3rd Intl. Symp. on *High-Temp. Superconductors: Processing and Microstructure Property Relationships*, The Metallurgical Society Mtg. and Exhibition, New Orleans, LA, Feb. 17-21, 1991.

Role of Oxygen Partial Pressure in Microstructural Development and Properties of YBCO Superconductors

J. P. Singh, R. Guttschow, J. T. Dusek, and R. B. Poeppel

To be presented at 93rd Annual Mtg. of the Am. Ceram. Soc., Cincinnati, OH, Apr. 28-May 2, 1991.

Effect of Silica and Processing Environment on the Toughness of Alumina Composites

S. M. Smith (North Carolina State University), R. O. Scattergood (NCSU), J. P. Singh, and K. Karasek (Allied-Signal, Inc.)

J. Am. Ceram. Soc. 72(7), 1252-1255 (July 1989).

Melt Processing $\text{YBa}_2\text{Cu}_3\text{O}_x$ Superconductors

T. Suratwala, U. Balachandran, C. A. Youngdahl, and R. B. Poeppel

To be presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc.,
Cincinnati, OH, Apr. 28-May 2, 1991.

Preparation of Lead Doped BSCCO Fine Powder Through a Novel Solution Technique

H. K. Varma (Regional Research Laboratory), K. G. K. Warriar (Reg. Res. Lab.), A. D. Damodaran (Reg. Res. Lab.), and U. Balachandran

To be presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc.,
Cincinnati, OH, Apr. 28-May 2, 1991.

High-Temperature Deformation of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$

A. W. von Stumberg, N. Chen, K. C. Goretti, and J. L. Routbort

J. Appl. Phys. 66(5), 2079-2082 (September 1, 1989).

Connected-Grain Model for Mechanical and Fracture Properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductors

A. S. Wagh (University of the West Indies) and J. P. Singh

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April
22-26, 1990.

Open Pore Description of Mechanical Properties of Ceramics

Arun S. Wagh (University of the West Indies) R. B. Poeppel, and J. P. Singh
Submitted to J. Mater. Sci.

Density Dependence of Thermal Conductivity in Alumina

A. S. Wagh (University of the West Indies), J. P. Singh, and R. B. Poeppel

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc.

Mechanical Properties of Ceramics for Pyrochemical Processes

A. S. Wagh (University of the West Indies), D. Roberts, T. Suratwala, and R. B. Poeppel

To be presented at 93rd Ann. Mtg. of the Am. Ceram. Soc.

Silver Sheathing of High-Temperature Superconductor Wires

C.-T. Wu, M. J. McGuire (University of Illinois at Chicago), G. A. Risch, R. B. Poeppel, K.

C. Goretti, H. M. Herro (Nalco Chemical Co.), and S. Danyluk (UIC)

To be presented at World Congress on *Superconductivity*, Houston, TX, Sept. 9-13,
1990.

Silver Sheathing of High- T_c Superconductor Wires

C.-T. Wu, M. J. McGuire (University of Illinois at Chicago), G. A. Risch, R. B. Poeppel, K.

C. Goretti, H. M. Herro (Nalco Chemical Co.), and S. Danyluk (UIC)

To be published in Proc. 2nd World Congress on *Superconductivity*, Houston, TX,
Sept. 9-13, 1990.

Design and Testing of a High-Temperature Superconducting Electrical Lead

J. L. Wu (Westinghouse Science and Technology Center), J. T. Dederer (WSTC), P. W. Eckels (WSTC), S. K. Singh (WSTC), J. R. Hull, R. Poeppel, C. Youngdahl, J. P. Singh, M. Lanagan, and U. Balachandran

To be presented at 1990 *Applied Superconductivity* Conf., Aspen, CO, Sept. 24-28, 1990.

Design and Testing of a High-Temperature Superconducting Current Lead

J. L. Wu (Westinghouse Science and Technology Center), J. T. Dederer (WSTC), P. W. Eckels (WSTC), S. K. Singh (WSTC), J. R. Hull, R. B. Poeppel, C. A. Youngdahl, J. P. Singh, M. T. Lanagan, and U. Balachandran

To be presented at 1990 *Applied Superconductivity*, Snowmass Village, CO, Sept. 24-28, 1990, Proc. to be published in IEEE Trans. Magn.

Erosion of Al and Al/SiC

W. Wu, K. C. Goretti, P. K. Rohatgi (University of Wisconsin at Milwaukee), S. Mostovoy (Illinois Institute of Technology), and J. L. Routbort

Proc. Industry-University *Advanced Materials* Conf. II, Golden, CO, March 6-9, 1989, ed. R. W. Smith, Advanced Materials Institute, Golden, CO, 1989, pp. 100-107.

Synthesis and Fabrication of High- T_c Films by a Sol-Gel Process

W. Wu, M. Kullberg (Amoco Chemical Co.), M. T. Lanagan, S. Danyluk (University of Illinois at Chicago)

To be presented at Amoco/University Poster Session, Naperville, IL, Oct. 5, 1990.

Texture of $YBa_2Cu_3O_{7-x}$ Superconductor Thick Films

W. Wu (University of Illinois at Chicago), S. Danyluk (UIC), M. Kullberg (Amoco Chemical Co.), M. T. Lanagan, and R. B. Poeppel

To be presented at 93rd Ann. Mtg., of the Amer. Ceram. Soc., Cincinnati, OH, Apr. 28-May 3, 1991.

The Effect of Wet- CO_2 Containing Atmosphere during Processing of YBCO Superconductors

D. Xu, U. Balachandran, S. E. Dorris, R. B. Poeppel, and G. Selvaduray (San Jose State University)

To be presented at 93rd Ann. Mtg. of the Amer. Ceram. Soc., Cincinnati, OH, Apr. 28-May 3, 1991.

Effect of CO_2 on Superconducting Properties of YBCO

C. Zhang, U. Balachandran, Y. Gao, Y. Li, K. L. Merkle, J. N. Mundy, and R. B. Poeppel

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Effect of CO_2 on Superconducting Properties of YBCO

C. Zhang, U. Balachandran (MCT), Y. Gao, Y. Li, K. L. Merkle, J. N. Mundy, R. B. Poeppel (MCT), and G. Selvaduray (San Jose State University)

Submitted to the 92nd Annual Mtg. of the Amer. Ceram. Soc., Dallas TX, April 22-26, 1990.

Patents**Method for Preparing Corrosion-Resistant Ceramic Shapes**

R. M. Arons and J. T. Dusek

U. S. Patent No. 4,404,154 awarded September 13, 1983.

Formation of Thin Walled Ceramic Solid Oxide Fuel Cells

Terry D. Claar, Donald E. Busch, and John J. Picciolo

U.S. Patent No. 4,883,497 awarded Nov. 29, 1989.

Monolithic Solid Electrolyte Oxygen Pump

D. C. Fee, R. B. Poeppel, T. E. Easier, and D. W. Dees

U. S. Patent No. 4,877,506 awarded October 31, 1989.

Porous Electrolyte Retainer for Molten Carbonate Fuel Cell

R. N. Singh and J. T. Dusek

U.S. Patent No. 4,389,467 awarded June 21, 1983.

Corrosion

Section Manager: T. F. Kassner

Principal Investigators: O. K. Chopra, H. M. Chung, A. B. Hull, B. A. Loomis,

K. Natesan, J. H. Park, W. E. Ruther, D. Y. Wang

Support Staff: A. Sather,¹ W. K. Soppet

Technicians: R. A. Clark, G. M. Dragel, L. J. Nowicki, and D. L. Rink

Secretary: S. M. Hagamann²

Visiting Scientist: A. U. Malik³

Students: A. P. Acosta,⁴ F. El Azem,⁵ B. Banks,⁶ L. Y. Bush,⁷ C. E. Campbell,⁸

M. R. Fox,⁹ J. Gazda,⁴ H. G. Khalak,¹⁰ C. A. Marsh,¹¹ J. W. Pascoe,¹⁰

A. B. Patel,¹⁰ C. Wasserfuhr,⁵ M. Widera,⁵ R. Zottmeier⁵

Programs of the Corrosion Section address specific concerns related to corrosion and the effect of various environments on the mechanical behavior of materials used in several types of energy systems. The section's research is sponsored by various divisions of the Department of Energy and the Nuclear Regulatory Commission, although industry-sponsored projects are also undertaken with DOE approval. Research on aqueous, gaseous, and liquid-metal corrosion, thermodynamics and kinetics of gas-solid reactions, and high-temperature mechanical properties in four major program areas is summarized below.

Light-Water Reactors

Stress Corrosion Cracking of Austenitic Stainless and Ferritic Steels in Simulated Coolant Environments

Environmentally assisted cracking of piping, in-core components, and pressure vessels in light-water reactors (LWRs) is an important concern as extended reactor lifetimes are envisaged. Cracking of weld-sensitized Type 304 stainless steel (SS) piping in boiling-water reactors (BWRs) has been mitigated largely by hydrogen/water chemistry and improved water purity. However, cracks that initiate in sensitized SS safe ends and SS cladding have propagated into low-alloy ferritic steel nozzles and pressure vessels, and extensive cracking has occurred in upper shell-to-transition cone girth welds in nonclad pressurized water reactor (PWR) steam generator vessels. Incidents of cracking of

¹Special Term Appointee.

²Serves two sections.

³Fulbright Scholar, India.

⁴University of Illinois at Chicago.

⁵Kernforschungszentrum Karlsruhe.

⁶Massachusetts Institute of Technology.

⁷University of Cincinnati.

⁸Northwestern University.

⁹Purdue University.

¹⁰SUNY-Buffalo.

¹¹Lewis University.

nonsensitized SS in BWR and PWR core-internal components have become more frequent as the plants age and fast-neutron fluence increases. As part of an NRC-sponsored program on environmentally assisted cracking in light-water reactor systems, we are evaluating the effect of simulated BWR water on the stress corrosion cracking (SCC) of low-alloy ferritic steel clad with Incoloy-182 weld metal. Factors that contribute to irradiation-assisted stress-corrosion cracking (IASCC) of commercial- and high-purity austenitic SS are also being investigated.

Crack-growth tests are being conducted on fracture-mechanics-type specimens under high-load-ratio, low-frequency loading conditions at 289°C. Crack growth in Inconel-182 weld metal occurs at virtually the same rate as in sensitized Type 304 SS under similar loading conditions.

Crack growth in the underlying A533-Gr B steel can be characterized by long periods (>800 h) of relatively slow growth interrupted by short intervals (<170 h) of rapid (transient) crack extension. The transient crack jumps (≈ 2 mm) are comparable to the monotonic plastic zone ahead of the crack, which suggests that a hydrogen-assisted cracking mechanism could be responsible for the transient growth. This phenomenon is being investigated further to quantify the periodic nature of the large crack extensions and their implications for the integrity of reactor vessels.

Radiation-induced segregation (RIS) of alloying and impurity elements in austenitic steels irradiated to high fluence in BWRs and PWRs is being investigated by scanning Auger microscopy to determine its role in IASCC of the steels. The graph below shows that the

Comparison of Cr-depletion profiles obtained by scanning Auger analyses of intergranular fracture surfaces of commercial- and high-purity Type 304 SS cladding from B₄C adsorber rods irradiated to high-fluence levels in BWRs

extent of chromium depletion near a grain boundary in high-purity Type 304 SS is considerably higher than that in a commercial-purity steel irradiated to the same fluence. SCC tests are being conducted on irradiated specimens of the same heats of steel to correlate RIS with cracking susceptibility in simulated BWR water.

Long-Term Embrittlement of Cast Duplex Stainless Steels

Cast stainless steels used in LWR systems for primary pressure-boundary components (such as valve bodies, pump casings, and primary coolant piping) undergo substantial reductions in fracture toughness after extended service at reactor operating temperatures. Charpy-impact, tensile, and static fracture-toughness (J-R curve) tests have been conducted on materials that were aged in the laboratory for up to 30,000 h and on materials obtained from two decommissioned reactors. Microstructures of the aged materials were characterized by high-voltage transmission electron microscopy (HVEM), small-angle neutron scattering (SANS), and field-ion atom probe (FIAP) techniques to identify the mechanism of embrittlement and validate the simulation of in-reactor degradation by accelerated-aging studies. The precipitation of additional phases in the ferrite matrix, e.g., a Cr-rich α' phase that forms by spinodal decomposition and an Ni- and Si-rich G phase, and precipitation and/or growth of carbides and nitrides at the ferrite/austenite phase boundaries are the primary cause of embrittlement in cast stainless steels. In general, the results indicate that the low-carbon CF-3 grades of cast stainless steels are the most resistant to low-temperature embrittlement and the Mn-containing high-carbon CF-8M grades are the most susceptible.

A methodology and correlations have been developed for predicting the fracture-toughness J-R curves and impact strength of cast components of known composition as a function of time and temperature during reactor service. On the basis of information from numerous heats of steel, a common "lower-bound" J-R curve for cast steels of unknown chemical composition has been defined for different grades of the steel and temperature of service. The figure on the next page shows the experimental and estimated J-R curves for CF-8M steel aged for 30,000 h at 290°C; the estimated J-R curves after 32 full power years of service and at saturation are shown as dashed lines. Our work provides a technical basis for an assessment of toughness loss for leak-before-break analyses of coolant-pressure boundaries, as well as insight into whether thermal aging of the steels will be a limiting factor in extension of nuclear-plant life to beyond ~40 years.

Radiation Embrittlement of Materials after Service in Light-Water Reactors

To better understand the metallurgical phenomena and mechanical-property degradation that can occur in reactor support structures during plant lifetimes, we investigated the low-temperature, low-fluence-rate embrittlement of ASTM A212 grade ferritic steel from the neutron shield tank (NST) of the Shippingport Reactor. The material was characterized by optical microscopy, through-wall microhardness measurements, and tensile and Charpy-impact tests. Irradiation embrittlement of the Shippingport NST is significantly lower than that expected on the basis of results from the High Flux Irradiation Reactor (HFIR) surveillance samples. The results for the NST material are consistent with the data from specimens irradiated in test reactors and agree very well with the correlations of the

Experimental and estimated J-R curves for aged static cast plate of CF-8M steel

shift in Charpy transition temperature, increase in tensile yield stress, and increase in hardness that have been developed for pressure vessel steels. Annealing studies indicate a complete recovery from embrittlement after 1 h at 400°C. High flux irradiation experiments have been planned for Shippingport NST and HFIR vessel materials, to evaluate possible effects of metallurgical and compositional differences (e.g., Cu content) between the two materials. Further tests will be carried out to seek an explanation for the apparent differences between the HFIR material and Shippingport NST and for exploration of alternative damage mechanisms.

Heavy-Water Reactors

New Production Reactor (NPR) Vessel and Piping Integrity Study

SCC tests are being conducted on candidate austenitic SSs for the piping and vessel of the NPR. Although SCC work under BWR conditions has greatly increased understanding of this phenomenon, the environment of the NPR is significantly different from that of a BWR. The additional testing will establish limits on the concentration of detrimental impurities in the water and provide assurance that the materials will have adequate resistance to SCC in the NPR. The crack-growth-rate data base for candidate materials will be used to carry out fracture mechanics analyses required to demonstrate adequate margin against leakage and/or sudden catastrophic failure of the vessel or piping system.

Fossil Energy

Corrosion Behavior of Commercial and Model Alloys/Coatings in Coal Conversion, Combustion, and MHD Power Generation Systems

Studies of the high-temperature corrosion of metallic materials are being conducted in simulated coal-gasification, fluidized-bed-combustion, and magnetohydrodynamic (MHD) power generation environments to establish mechanisms of corrosion, predict the onset of breakaway corrosion, and evaluate the role of stress and deformation in the corrosion process. The sulfidation resistance of model Fe-Cr, Fe-Cr-Ni, and Fe-Cr-Al alloys with controlled additions of several refractory metals and rare earth elements is being evaluated by thermogravimetric tests and postexposure microstructural characterization of corrosion scales by several electron/optical microscope techniques. Alloy additions are made by bulk alloying, ion implantation, sputter deposit/ion-beam mixing, and by coating. In-situ electrochemical measurements on thermally grown oxide scales yield information on the ionic transport properties of the layers.

In gasification environments, cation transport in the corrosion-product scales is the dominant factor in the initiation of breakaway corrosion. In combustion atmospheres, however, molecular transport of SO_2 from the gas phase plays a critical role in this phenomenon. Studies of Zr- and Nb-modified Fe-Cr-Ni alloys showed that these additions led to the formation of an Nb- or Zr-oxide layer at the scale/metal interface. This layer minimizes oxidation-induced voids in this region and thereby reduces the depth of internal sulfidation of the substrate alloys and promotes the formation of a continuous layer of Cr_2O_3 . The internal layer acts as a barrier to transport of base-metal cations outward and gas-phase anions inward and extends the time to breakaway corrosion. The SEM micrographs show the scale underside of a specimen of Fe-25 wt.% Cr-20 wt.% Ni-3 wt.% Zr alloy after exposure to a sulfur-free low- pO_2 environment at 875°C . Light regions are predominantly Zr-oxide and seem to have formed in regions containing intermetallic particles, where the oxide is aligned with the rolling direction of the substrate alloy. The magnified micrographs (top right and bottom left) show that the ZrO_2 phase grew from the back side of the Cr_2O_3 (smooth region between ridges), and an additional phase of (Cr,Zr) oxide was observed between the ZrO_2 (light) and Cr_2O_3 (smooth) phases. The lower right micrograph shows the sample in 45° tilt position and indicates that the ZrO_2 is in filament form and projects into the alloy. Additions of Nb via an ion-implantation route also stabilized the Cr_2O_3 scale and substantially reduced the corrosion rate.

In coal combustion systems, CaSO_4 deposits, which form when limestone is used to reduce sulfur emissions during fluidized-bed combustion of coal, seem to enhance the formation of corrosion-product scales on Types 304 and 316 SS. But the deposits can trigger internal sulfidation, which may degrade alloy performance in the long run. Chromized stainless steel, CoCrAlY-coated Alloy 800H, and Fe-based aluminide exhibit good corrosion resistance in the presence of CaSO_4 deposits.

Scale-Metal Interface

*SEM photographs of scale side of scale/metal interface on
Fe-25 wt.% Cr-20 wt.% Ni-3 wt.% Zr after exposure to
sulfur-free low- pO_2 environment at 875°C*

Fusion Energy

Effects of Simulated Fusion Reactor Environments on Corrosion and Mechanical Properties of Candidate Structural Materials

Structural materials in a fusion reactor will be cooled by an aqueous or liquid-metal coolant while undergoing displacement damage and transmutation reactions that produce hydrogen and helium atoms within the materials because of 14 MeV-neutron irradiation. An austenitic SS will be the structural material for the International Thermonuclear Experimental Reactor (ITER), whereas either a ferritic steel or a vanadium-base alloy is the likely candidate for subsequent power-producing fusion reactors.

Current research is directed toward the acquisition of material-property data for design and construction of the ITER and subsequent reactors. Study subjects include aqueous SCC of austenitic SSs in oxygenated water (with and without hydrogen charging of the steels), aqueous corrosion and embrittlement of niobium-base alloys for divertor applications, corrosion of vanadium-base alloys in liquid lithium, and evaluations of the tensile, creep, fracture-toughness, and swelling properties of vanadium-base alloys after fast-neutron irradiation in the Fast-Flux Test Facility at 420 and 600°C. On the basis of present results, the V-5% Cr-5% Ti alloy appears to be the most promising candidate. Transmission electron microscopy evaluations are being performed on the irradiated and nonirradiated alloys to interpret the mechanical-property information and to optimize a structural alloy for fusion reactor designs with a lithium blanket and coolant.

Recent Work by the Corrosion Section

Publications

Practical Superconductor Development for Electrical Power Applications, Annual Report for FY 1988

U. Balachandran, I. D. Bloom (CMT), S. E. Dorris, J. T. Dusek, J. E. Emerson, K. C. Goretta, K. E. Gray, J. R. Hull, R. T. Kampwirth, M. T. Lanagan, H. J. Leu, V. A. Maroni, R. L. McDaniel, J. J. Picciolo, J. P. Singh, L. R. Turner, and C. A. Youngdahl
ANL-88-37 (February 1989).

Embrittlement of Cast Stainless Steels in LWR Systems

O. K. Chopra and H. M. Chung

Presented at 15th MPa Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.

Irradiation Embrittlement of the Shippingport Neutron Shield Tank

O. K. Chopra and W. J. Shack

Presented at 15th MPa Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.

Embrittlement of Cast Stainless Steels in LWR Systems

O. K. Chopra and H. M. Chung

To be published in Proc. 15th MPa Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.

Irradiation Embrittlement of the Shippingport Neutron Shield Tank

O. K. Chopra and W. J. Shack

To be published in Proc. 15th MPa Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.

Cast Stainless Steel Aging: Mechanisms and Predictions

O. K. Chopra and H. M. Chung

To be presented at the 17th *Water Reactor Safety Information Mtg.*, Rockville, MD, October 23-25, 1989.

Embrittlement of the Shippingport Reactor Shield Tank

O. K. Chopra and W. J. Shack

To be presented at the 17th *Water Reactor Safety Information Mtg.*, Rockville, MD, October 23-25, 1989.

Cast Stainless Steel Aging: Mechanisms and Predictions

O. K. Chopra and H. M. Chung

To be published in Proc. 17th *Water Reactor Safety Information Mtg.*, Rockville, MD, October 23-25, 1989.

Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems: Semiannual Report, April-September 1987

O. K. Chopra and H. M. Chung

NUREG/CR-4744 Vol. 2, No. 2; ANL-89/6 (June 1989).

Thermal Aging of Cast Stainless Steels: Mechanisms and Predictions

O. K. Chopra

Presented at the 1990 ASME *Pressure Vessels and Piping Conf.*, Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990.

Embrittlement of the Shippingport Reactor Neutron Shield Tank

O. K. Chopra, S. T. Rosinski (Sandia National Laboratories), and W. J. Shack

Presented at the 1990 ASME *Pressure Vessels and Piping Conf.*, Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990.

Embrittlement of the Shippingport Reactor Neutron Shield Tank

O. K. Chopra, S. T. Rosinski (Sandia National Laboratories), and W. J. Shack

Fatigue, Degradation, and Fractures, ed. W. H. Bamford, C. Becht IV, S. B. Framatome, J. D. Gilman, L. A. James, and M. Prager. (Proc. 1990 ASME *Pressure Vessels and Piping Conf.*, Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990), The American Society of Mechanical Engineers, New York, NY (1990), PVP-Vol. 195, pp. 157-168.

Thermal Aging of Cast Stainless Steels: Mechanisms and Predictions

O. K. Chopra

Fatigue, Degradation, and Fractures, ed. W. H. Bamford, C. Becht IV, S. B. Framatome, J. D. Gilman, L. A. James, and M. Prager (Proc. 1990 ASME *Pressure Vessels and Piping Conf.*, Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990), The American Society of Mechanical Engineers, New York, (1990), PVP-Vol. 195, pp. 193-214.

Studies of Aged Cast Stainless Steel from the Shippingport Reactor

O. K. Chopra and H. M. Chung

To be presented at 18th *Water Reactor Safety Information Mtg.*, Rockville, MD, Oct. 22-24, 1990.

Estimation of Fracture Toughness of Cast Stainless Steels in LWR Systems

O. K. Chopra

To be presented at 18th *Water Reactor Safety Information Mtg.*, Rockville, MD, Oct. 22-24, 1990.

Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems - Semiannual Report for the Period April-September 1988

O. K. Chopra and H. M. Chung

NUREG/CR-4744, ANL-90/5, Vol. 3, No. 2, R5 (August 1990).

Initial Assessment of the Mechanisms and Significance of Low-Temperature Embrittlement of Cast Stainless Steels in LWR Systems

O. K. Chopra and A. Sather

NUREG/CR-5385, ANL-89/17 (August 1990).

Studies of Aged Cast Stainless Steel from the Shippingport Reactor

O. K. Chopra

INVITED PAPER: to be presented at 18th *Water Reactor Safety Information Mtg.*, Rockville, MD, Oct. 22-24, 1990.

Estimation of Fracture Toughness of Cast Stainless Steels in LWR Systems

O. K. Chopra

INVITED PAPER: to be presented at 18th *Water Reactor Safety Information Mtg.*, Rockville, MD, Oct. 22-24, 1990.

Mechanical Properties and Microstructure of Si_3N_4 Whisker-Reinforced Si_3N_4 Matrix Composite

C. Y. Chu and J. P. Singh

To be presented at the 14th Ann. Conf. on *Composites and Advanced Ceramics*, Cocoa Beach, FL, January 14-17, 1990.

Thermal Aging of Decommissioned Reactor Cast Stainless Steel Components and Methodology for Life Prediction

H. M. Chung

INVITED PAPER: Proc. ASME Material Properties Council Symp. on *Plant Life Extension for Nuclear Components*, Honolulu, HI, July 24-27, 1989, American Society of Mechanical Engineers, New York, 1989, PVP, Vol. 171, pp. 111-125.

Accelerated Aging Embrittlement of Cast Duplex Stainless Steel - Activation Energy for Extrapolation

H. M. Chung and O. K. Chopra

To be published in Proc. 4th Intl. Symp. on *Environmental Degradation of Materials in Nuclear Power Systems -- Water Reactors*, Jekyll Island, GA, August 6-10, 1989.

Embrittlement of Laboratory- and Reactor-Aged CF-3, CF-8, and CF-8M Duplex Stainless Steels

H. M. Chung and T. R. Leax (Westinghouse Electric Corp.)

Mater. Sci. Technol., Vol. 6, pp. 249-262, (March 1990).

Correlation of Waterside Corrosion and Cladding Microstructure in High-Burnup Fuel and Gadolinia Rods

H. M. Chung

INVITED PAPER: Proc. International Atomic Energy Agency Technical Committee Mtg. on *Fundamental Aspects of Corrosion of Zirconium-Base Alloys in Water Reactor Environments*, Portland, OR, September 11-15, 1989, The International Atomic Energy Agency, Vienna, 1990, IWGFPT/34, pp. 201-211.

Spinodal-like Decomposition of Austenite in Long-Term-Aged Duplex Stainless Steel

H. M. Chung

Physical Metallurgy of Controlled Expansion Invar-Type Alloys, ed. K. C. Russell and D. F. Smith (Proc. Metallurgical Society Ann. Mtg., Las Vegas, NV, February 27-March 3, 1989), The Minerals, Metals, and Materials Society, Warrendale, PA, (1990), pp. 129-141.

Evaluation and Diagnosis of Aging of Cast Stainless Steel Components

Chung, H. M.

INVITED TALK to be presented at ASME *Vessel and Piping* Conf., San Diego, CA, June 23-27, 1991.

Irradiation-Induced Sensitization in Austenitic Stainless Steel of In-Core Components

H. M. Chung, W. E. Ruther, D. Y. Wang, and T. F. Kassner

To be presented at 18th *Water Reactor Safety Information* Mtg., Rockville, MD, Oct. 22-24, 1990.

Irradiation-Induced Sensitization in Austenitic Stainless Steel of In-Core Components

H. M. Chung, W. E. Ruther, D.-Y. Wang, and T. F. Kassner

To be presented at 18th *Water Reactor Safety Information* Mtg., Rockville, MD, Oct. 22-24, 1990.

Y₂BaCuO₅ as a Substrate for YBa₂Cu₃O_x

S. E. Dorris, M. T. Lanagan, D. M. Moffatt (Pennsylvania State University), H. J. Leu, C. A. Youngdahl, U. Balachandran, A. Cazzato, D. E. Bloomberg, and K. C. Goretti
Jpn. J. Appl. Phys. 28(8), L 1415-L 1416 (August 1989).

Fabrication of Superconductor Coils

S. E. Dorris, J. T. Dusek, J. J. Picciolo, H. J. Leu, J. P. Singh, A. Cazzato, and R. B. Poeppel

To be published in Proc. First Intl. *Ceram. Sci. and Technol.* Congress, Anaheim, CA, October 31-November 3, 1989.

Stress Corrosion Cracking of Candidate Structural Materials under Simulated First-Wall/Aqueous Coolant Environments

M. R. Fox, A. B. Hull, and T. F. Kassner

To be published in Proc. 9th ANS Topical Mtg., of Fusion Energy, Oak Brook, IL, Oct. 7-11, 1990.

Microstructural Explanation for Irradiation Embrittlement of V-15Cr-5Ti

D. S. Gelles (Pacific Northwest Laboratory), S. Ohnuki (Hokkaido University), B. A. Loomis, H. Takahashi (Hokkaido U.), and F. A. Garner

Presented at Intl. Conf. on *Fusion Reactor Materials* 4, Kyoto, Japan, December 4-8, 1989.

Microstructural Explanation for Irradiation Embrittlement of V-15Cr-5Ti

D. S. Gelles (Pacific Northwest Laboratory), S. Ohnuki (Hokkaido University), B. A. Loomis, H. Takahashi (Hokkaido U.), and F. A. Garner

To be published in Proc. Intl. Conf. on *Fusion Reactor Materials* 4, Kyoto, Japan, December 4-8, 1989.

Microstructural Explanation for Irradiation Embrittlement of V-15Cr-5Ti

D. S. Gelles (Pacific Northwest Laboratory), S. Ohnuki (Hokkaido University), B. A. Loomis, H. Takahashi (Hokkaido U.), and F. A. Garner

Fusion Reactor Materials Semiannual Progress Report for the Period Ending September 30, 1989, DOE/ER-0313/7, in press.

Impact Behavior of Irradiated V-15Cr-5Ti following Hydrogen Removal

M. L. Hamilton (Pacific Northwest Laboratory) and B. A. Loomis

Fusion Reactor Materials Semiannual Progress Report for the Period Ending September 30, 1989, DOE/ER-0313/7 (1990) 190-192.

Materials Considerations for the Prototypical MHD Coal Combustor

L. E. Hill (TRW), R. I. Batista (TRW), T. Koyama (TRW), G. Litvinsky (TRW), K. Natesan, and D. Y. Wang

Proc. 27th Symp. on *Engineering Aspects of Magnetohydrodynamics*, Reno, NV, June 27-29, 1989, ed. J. Martin Bauer, TRW, Inc., Cleveland, OH, 1989, pp. 8.17-1-8.17-9.

Carbon Transfer in Lithium/Structural-Material Systems

A. B. Hull, O.K. Chopra, and A. B. Patel

Contribution to Fusion Reactor Materials Semiannual Report for the Period Ending September, 1989, DOE-ER-031317, pp. 242-249 (1990).

Compatibility between Vanadium-Base Alloys and Flowing Lithium: Partitioning of Hydrogen at Elevated Temperatures

A. B. Hull, O. K. Chopra, B. Loomis, and D. Smith (FPP)

To be published in Proc. 4th Intl. Conf. on *Fusion Reactor Materials* (ICFRM-4), Kyoto, Japan, December 4-8, 1989.

Stress Corrosion Cracking of Candidate Structural Materials under Simulated First-Wall/Aqueous Coolant Environments

A. B. Hull, M. Fox, and T. F. Kassner

To be presented at 9th Topical Mtg. on *Techn. of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Compatibility between Vanadium-Base Alloys and Flowing Lithium: Partitioning of Hydrogen at Elevated Temperatures

A. B. Hull, O. K. Chopra, B. Loomis, and D. Smith (FPP)

Contribution to Fusion Reactor Materials Semiannual Report for the Period Ending March 31, 1990; DOE/ER-0313/8, in press.

Environmental Effects on Aqueous Stress Corrosion of Candidate Austenitic Steels for ITER Structural Applications

A. B. Hull, M. R. Fox, J. W. Pascoe, and T. F. Kassner

Fusion Reactor Materials Semiannual Progress Report for the Period Ending Sept. 30, 1990, DOE-ER/0313/9, in press.

Characteristics of Autoclave and In-Reactor Nodular Corrosion

Y. H. Jeong (Advanced Energy Research Institute), K. S. Rheem (AERI), and H. M. Chung

To be presented at the 9th Intl. Symp. on *Zirconium in the Nuclear Industry*, Kobe, Japan, November 5-8, 1990.

Mitigation of Stress Corrosion Cracking of AISI 304 Stainless Steel by Organic Species at Low Concentration in Oxygenated Water at 289C

T. F. Kassner, W. E. Ruther, and W. K. Soppet

To be published in Proc. *CORROSION/90*, Las Vegas, NV, April 23-27, 1990.

Environmentally Assisted Cracking in Light Water Reactors

T. F. Kassner, J. Y. Park, W. E. Ruther, and W. J. Shack

To be published in Proc. 17th *Water Reactor Safety* Information Mtg., Rockville, MD, October 23-25, 1989.

Environmentally Assisted Cracking of Austenitic and Ferritic Steels in Simulated BWR Water

T. F. Kassner, J. Y. Park, W. E. Ruther, W. K. Soppet, and W. J. Shack

INVITED PAPER to be published in *Nucl. Eng. Des.*

The Atmospheric Fluidized-Bed Cogeneration Air Heater Experiment

A. Klein (Energy Technology Engineering Center), K. Natesan, and W. F. Podolski (CMT)

Proc. 1989 Intl. Conf. on *Fluidized Bed Combustion*, San Francisco, CA, April 30-May 3, 1989, ed. Arnold M. Manaker, The American Society of Mechanical Engineers, New York, 1989, Vol. 2, pp. 1319-1324.

Background Aspects of Lake Restoration: Water Balance, Heavy Metal Content, Phosphorus Homeostasis

A. Lerman (Northwestern University), and A. B. Hull (Northwestern U.)

Proc. International Conf. on *Lake Restoration of Zurich*, Nov. 3-4, 1986, Schweiz, *Z. Hydrol*, 49 (2) (1987).

Fabrication of a Superconducting Coil for Solenoid Applications

H. J. Leu, J. P. Singh, S. E. Dorris, and R. B. Poeppel

Submitted to *Supercond. Sci. Technol.*

Sintering Stress Analysis of Monolithic Solid Oxide Fuel Cell Tapes

H. J. Leu and S. Majumdar

Submitted to *J. Am. Ceram. Soc.*

Evaluation of Low-Activation Vanadium Alloys for Use as Structural Material in Fusion Reactors

B. A. Loomis, A. B. Hull, and D. L. Smith (FPP)

To be published in Proc. 4th Intl. Conf. on *Fusion Reactor Materials*, Kyoto, Japan, December 4-8, 1989.

Tensile Properties for Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith (FPP)

Fusion Reactor Materials Semiannual Progress Report for the Period Ending September 30, 1989, DOE/ER-0313/7 (1990) 203-209.

Relationship of Microstructure and Tensile Properties for Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith (FPP)

To be presented at the 15th Symp. on *Effects of Radiation on Materials*, Nashville, TN, June 17-21, 1990.

Swelling Dependence of Neutron-Irradiated Vanadium Alloys on Temperature, Neutron Fluence, and Thermochemical Treatment

B. A. Loomis and D. L. Smith (Fusion Power Program)

To be presented at 9th Topical Mtg. on *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Relationship of Microstructure and Tensile Properties for Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith (FPP)

To be presented at 15th Intl. Symp. on *Effects of Radiation on Materials*, Nashville, TN, June 18-22, 1990.

Relationship of Microstructure and Tensile Properties for Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith (FPP)

Contribution to Fusion Reactor Materials Semiannual Report for the Period Ending March 31, 1990; DOE/ER-0313/8, in press.

Swelling and Tensile Properties of Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith

To be presented at the Conf. on *Effect of Irradiation on Materials of Fusion Reactors*, Leningrad, USSR, Sept. 18-20, 1990.

Swelling and Tensile Properties of Neutron-Irradiated Vanadium Alloys

B. A. Loomis and D. L. Smith

To be presented at Conf. on *Effect of Irradiation on Materials of Fusion Reactors*, Leningrad, USSR, Sept. 18-20, 1990.

Swelling Dependence of Neutron-Irradiated Vanadium Alloys on Temperature, Neutron Fluence, and Thermomechanical Treatment

B. A. Loomis, K. Abe (Tohoku University), L. J. Nowicki, and D. L. Smith (FPP)
Fusion Reactor Materials Semiannual Progress Report for the Period Ending Sept. 30, 1990, DOE-ER/0313/9, in press.

Stress Corrosion Cracking of Candidate Materials for Nuclear Waste Containers

P. S. Maiya, W. J. Shack, and T. F. Kassner
INVITED PAPER: *Corrosion 90* (Proc. High Temperature Symp., Las Vegas, NV, April 23-27, 1990, National Association of Corrosion Engineers, Houston, TX, (1990), pp. 284/1-284/15.

High-Temperature Oxidation and Sulfidation of Fe-20Cr-16Ni-4Al-1Y₂O₃ Oxide-Dispersion-Strengthened Alloy

A. U. Malik (Aligarh Muslim University) and K. Natesan
ANL/FE-89/7 (October 1989).

Spectroscopic Characterization of Oxide Films on Type 304 SS Exposed to Water at 289°C: Correlation with the Fe-Cr-H₂O Pourbaix Diagram

V. A. Maroni, C. A. Melendres, T. F. Kassner, R. Kumar, and S. Siegel
J. of Nucl. Mater. 171, pp. 13-18, (1990).

Development of Alloys with Improved Oxidation-Sulfidation Resistance

K. Natesan and J. H. Park
INVITED TALK presented at 3rd Ann. *Fossil Energy Materials Program Contractors' Conf.*, Oak Ridge, TN, August 8-10, 1989; abstract in Program and Abstracts booklet, p. 57.

Corrosion Behavior of Materials for MHD Steam Bottoming Plant

K. Natesan and W. M. Swift (CMT)
Proc. 27th Symp. on *Engineering Aspects of Magnetohydrodynamics*, Reno, NV, June 27-29, 1989, ed. J. Martin Bauer, TRW, Inc., Cleveland, OH, 1989, pp. 3.2-1-3.2-10.

Erosion-Corrosion of Materials at Elevated Temperature

K. Natesan and Y. Y. Liu
INVITED PAPER: Mater. Sci Eng. A121, 571-580 (1989). (Proc. 2nd Intl. Symp. on *High-Temperature Corrosion of Advanced Materials and Coatings*, Les Embiez, France, May 22-26, 1989.

Role of Alloying Additions in the Oxidation-Sulfidation of Fe-Base Alloys

K. Natesan and J. H. Park
INVITED PAPER: Proc. Symp. on *Corrosion and Particle Erosion at High Temperatures*, TMS-AIME Annual Mtg., Las Vegas, NV, February 27-March 3, 1989, ed. V. Srinivasan and K. Vedula, The Minerals, Metals & Materials Society, 1989, Warrendale, PA, pp. 49-64.

Corrosion and Mechanical Properties of Alloys in FBC and Mixed-Gas Environments

K. Natesan and J. H. Park

Advanced Research and Technology Development Fossil Energy Materials Program:
Semiannual Progress Report for the Period Ending March 31, 1989, ORNL/FMP-
89/1 (July 1989), pp. 351-365.

Materials Selection for an MHD Steam Bottoming Plant

K. Natesan and W. M. Swift (CMT)

To be published in Proc. 10th Intl. Conf. on *MHD Electrical Power Generation*,
Tiruchirapalli, India, December 5-9, 1989.

Corrosion Comparison in Bubbling-Bed and Circulating Fluid-Bed Environments

K. Natesan

INVITED PAPER: Proc. Workshop *Materials Issues in Circulating Fluidized-Bed
Combustors*, Argonne National Laboratory, Argonne, IL, June 19-23, 1989, EPRI
GS-6747 (February 1990), pp. 31-1-31-20.

Evaluation of Materials for the MHD Steam Bottoming Plant

K. Natesan and W. M. Swift (CMT)

To be published in Proc. 24th IECEC Conf., Washington, DC, August 6-11, 1989.

Development of Coatings with Improved Corrosion Resistance in Sulfur-Containing Environments

K. Natesan and R. N. Johnson (Westinghouse Hanford Co.)

Presented at 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-6,
1990, abstract in Program and Abstracts booklet, p. A-14.

Materials Tests in Support of an MHD Coal Combustor

K. Natesan, D. Y. Wang, and W. K. Soppet

ANL/MHD-89/2 (November 1989).

Corrosion and Mechanical Properties of Alloys in FBC and Mixed-Gas Environments

K. Natesan and J. H. Park

Advanced Research and Technology Development Fossil Energy Materials Program:
Semiannual Progress Report for the Period Ending September 30, 1989,
ORNL/FMP-89/2, (January 1990) pp. 345-373.

Corrosion Behavior of Materials in FBC Environments

K. Natesan

Presented at AR&TD *Fossil Energy Materials Program Contractors Conf.*, Oak
Ridge, TN, May 15-17, 1990, abstract in Conf. Abstracts booklet, p. 53.

Corrosion Test Results and Materials Selection for a Prototypical MHD Coal Combustor

K. Natesan, D. Y. Wang, and G. Listvinsky (TRW, Inc.)

To be presented at the 28th Symp. on *Engineering Aspects of
Magnetohydrodynamics*, Chicago, IL, June 26-28, 1990.

Corrosion Behavior of Coatings in Sulfur-Containing Atmospheres

K. Natesan

To be presented at Symp. on *The Use of Surface Modification/Treatments/Coatings in High-Temperature Service*, ASM Mater. Week 1990, Detroit, MI, Oct. 8-11, 1990.

Assessment of Corrosion in FBC Systems

Natesan, K.

INVITED PAPER to be published in Proc. 4th Berkeley Conf. on *Corrosion-Erosion-Wear of Mater. at Elevated Temperatures*, Berkeley, CA, Jan 31-Feb 2, 1990.

Corrosion Test Results and Materials Selection for a Prototypical MHD Coal Combustor

K. Natesan, D. Y. Wang, and G. Listvinsky (TRW)

To be presented at 28th Symp. on *Engineering Aspects of Magnetohydrodynamics*, Chicago, IL, June 26-28, 1990.

Corrosion Behavior of Materials in FBC Environments

K. Natesan

Presented at AR&TD *Fossil Energy Materials Program Contractors Conf.*, Oak Ridge, TN, May 15-17, 1990.

Development of Coatings with Improved Corrosion Resistance in Sulfur-Containing Environments

K. Natesan and R. N. Johnson (Westinghouse Hanford Co.)

To be published in Proc. 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, Apr. 2-6, 1990.

The Role of Zr and Nb in Oxidation/Sulfidation Behavior of Fe-Cr-Ni Alloys

K. Natesan and D. J. Baxter (INCO Alloy Ltd., Hereford, England)

ANL/FE-90/2 (November 1990).

Laboratory Studies on Corrosion of Materials for Fluidized Bed Combustion Applications

K. Natesan

ANL/FE-90/1 (1990).

Development of Oxide-Dispersion-Strengthened Alloys for Fossil Energy Applications

K. Natesan

ANL/FE-89/6 (October 1989).

Microstructural Examination of Simple Vanadium Alloys Irradiated in the FFTF/MOTA

S. Ohnuki (Hokkaido U.), D. S. Gelles (Pacific Northwest Laboratory), B. A. Loomis, F. A. Garner (PNL), and H. Takahashi (Hokkaido U.)

Presented at Intl. Conf. on *Fusion Reactor Materials 4*, Kyoto, Japan, December 4-8, 1989.

Microstructural Examination of Simple Vanadium Alloys Irradiated in the FFTF/MOTA
S. Ohnuki (Hokkaido University), D. S. Gelles (Pacific Northwest Laboratory), B. A.
Loomis, F. A. Garner (PNL), and H. Takahashi (Hokkaido U.)

To be published in Proc. Intl. Conf. on *Fusion Reactor, Materials* 4, Kyoto, Japan,
December 4-8, 1989.

Microstructural Examination of Simple Vanadium Alloys Irradiated in the FFTF/MOTA
S. Ohnuki (Hokkaido University), D. S. Gelles (Pacific Northwest Laboratory), B. A.
Loomis, F. A. Garner (PNL), and H. Takahashi (Hokkaido U.)

Fusion Reactor Materials Semiannual Progress Report for the Period Ending
September 30, 1989, DOE/ER-0313/7 (1990), 177-189.

Electronic Transport in 8-Mole Percent Y_2O_3 - ZrO_2

J.-H. Park and R. N. Blumenthal (Marquette University)

J. Electrochem. Soc. 136(10), 2867-2876 (October 1989).

Thermodynamic Properties of Nonstoichiometric Yttria-stabilized Zirconia at Low Oxygen
Pressures

Jong-Hee Park and Robert N. Blumenthal (Marquette University)

J. Am. Ceram. Soc. 72(8), 1485-1487 (1989).

Transport Properties of Thermally Grown Cr_2O_3

J.-H. Park and K. Natesan

ANL/FE-89/5 (May 1989).

Role of Yttrium in Enhanced Adhesion of Chromia Scale to Chromium

J.-H. Park

Mater. Lett. 8(10), 405-408 (October 1989).

Measuring Oxygen Diffusivity and Solubility in Solid Silver with a Gas-Tight Electrochemical
Cell

J.-H. Park

Mater. Lett. 9 (9), 313-316 (May 1990).

Transport Properties in Chromium and Fe-Cr Alloys Exposed to Oxygen-Sulfur
Environments

J.-H. Park and K. Natesan

To be published in Proc. 4th Berkely Conf. on *Corrosion-Erosion Wear of Mater. at
Elevated Temp.*, Berkeley, CA, Jan 31-Feb 2, 1990.

Oxidation of Copper and Electronic Transport in Copper Oxides

J.-H. Park and K. Natesan

Presented at 178th Mtg. of Electrochemical Soc., Inc., Seattle, WA, Oct. 14-19,
1990, abstract No. 490 in Program Booklet.

Oxidation of Copper and Electronic Transport in Copper Oxides

J.-H. Park and K. Natesan

The Electrochemical Society, Inc., (Proc. Symp. on *High Temperature Materials Chemistry-V*, ed. William B. Johnson and Robert A. Rapp, The Electrochemical Society, Inc., Pennington, NJ, (1990), Vol 90-18, pp. 41-45.

Transport Properties and Oxidation in Chromium and Fe-Cr Alloys Exposed to Oxygen at High Temperatures

J.-H. Park and K. Natesan

To be presented at 1st Intl. Conf. on Materials, Lake Geneva, WI, Sept. 22-26, 1991.

Environmentally Assisted Cracking In Light Water Reactors

J. Y. Park, W. E. Ruther, T. F. Kassner, and W. J. Shack

To be published in Proc. 18th *Water Reactor Safety* Information Mtg., Rockville, MD, October 22-24, 1990.

Aqueous Stress Corrosion of Structural Materials

A. B. Patel, A. B. Hull, and T. F. Kassner

Contribution to Fusion Reactor Materials Semiannual Report for the Period Ending September 1989.

Atmospheric Fluidized Bed Cogeneration Air Heater Experiment

W. Podolski, K. Natesan, W. Gerritsen (Energy Technology Engineering Center), A. Stewart (ETEC), K. Robinson (ETEC)

To be presented at DOE Contractor's Review Mtg., Chicago, IL, Oct. 2-3, 1990.

Fabrication of Silver-Based Superconducting Coil for Solenoid Application

J. P. Singh, H. J. Leu, S. E. Dorris, and R. B. Poeppel

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

A New Calculational Method for Deducing the Complex Chemistry of Coal Ash Deposits

S. Sinha, K. Natesan, and M. Blander

Proc. Conf. on *Mineral Matter and Ash Deposition from Coal*, Santa Barbara, CA, February 22-26, 1988, eds. R. W. Bryers and K. S. Vorres, 117-126 (1990).

Chemistry of Gaseous and Condensed Products in Coal Combustion and Conversion Systems

S. N. Sinha, K. Natesan, and M. Blander

ANL-89/25 (August 1989).

Lithium Corrosion/Mass Transfer Test Facility

D. L. Smith (FPP), O. K. Chopra, and A. B. Hull

Fusion Eng. Des. 9, 339-345 (1989).

Corrosion Performance of High-Chromium Weldments of Chromized Low-Alloy Steels in Simulated Medium-Btu Coal Gasifier Atmospheres

D. Y. Wang

Presented at the High Temperature Symp., *Corrosion 90*, Las Vegas, NV, April 23-27, 1990.

Compatibility Study of Boron Nitride Insulator Coating with Liquid Lithium and Structural Materials

D. Y. Wang, A. B. Hull, and D. L. Smith (FPP)

To be presented at the 1990 TMS Ann. Mtg., Anaheim, CA, February 18-22, 1990.

Corrosion Evaluation of Weldments Exposed in TVA and Rocketdyne Atmospheric Fluidized Bed Combustors

D. Y. Wang and K. Natesan

INVITED PAPER *Corrosion 90 Proc High Temperature Symp.*, Las Vegas, NV, April 23-27, 1990, National Association of Corrosion Engineers, Houston, TX, (1990), pp. 284/1-284/15.

Corrosion Performance of High-Chromium Weldments in Simulated Medium-Btu Coal Gasifier Atmospheres

D. Y. Wang and K. Natesan

Corrosion 90 (Proc. High Temperature Symp., Las Vegas, NV, April 23-27, 1990), National Association of Corrosion Engineers, Houston, TX, (1990), Paper No. 282, pp. 282/1-282/12.

A Comparative Study of Iron-, Nickel-, and Cobalt-Base Weldments Exposed in TVA 20-MW and Rocketdyne Atmospheric Fluidized Bed Combustors

D. Y. Wang and K. Natesan

ANL-90/17 (June 1990).

Development of Ceramic Coatings for Liquid Metal Blanket Applications

D. Y. Wang, A. B. Hull, M. R. Fox, and C. E. Campbell

Fusion Reactor Materials Semiannual Progress Report for the Period Ending Sept. 30, 1990, DOE-ER/0313/9, in press.

Mechanics of Materials

Section Manager: D. R. Diercks

Principal Investigators: M. C. Billone, A. M. Hassanein, S. Majumdar, J. Y. Park,

J. Rest, H. R. Thresh, T. C. Wiencek

Support Staff: P. E. Domagala, S. A. Zawadzki

Postdoctoral Appointees: P. D. Hicks, C. C. Lin, A. Stojimirovic

Technicians: W. F. Burke, D. R. Schmitt, J. R. Summers, T. Galvin, C. F. Konicek,

D. R. Perkins, S. L. Phillips, F. E. Soppet, K. E. Stair, G. J. Talaber,

J. C. Tezak, J. A. Zic

Secretary: P. J. Peterson

Visiting Scientist: A. E. Dwight¹

The programs carried out by the Mechanics of Materials Section may be divided into three broad areas: (1) mechanical testing and component examination and analysis in support of light water reactor (LWR) technology, (2) mathematical modeling and analysis of structures and systems in support of nuclear and nonnuclear energy development, and (3) fabrication and nuclear fuel reprocessing. The third area reflects the incorporation (in 1990) of the former Fabrication Technology Section into the Mechanics of Materials Section. Current work in the first area includes an ongoing program on environmentally assisted cracking of LWR structural components, stress corrosion cracking (SCC) of candidate nuclear waste canister alloys, metallurgical examination and mechanical testing of material from the lower head of the Three Mile Island Unit 2 (TMI-2) nuclear reactor, and analysis of failed components from operating nuclear power plants.

In the second area, nuclear fuel behavior is being modeled for both LWRs and the Integral Fast Reactor (IFR), as well as for the Advanced Neutron Source (ANS). Analytical research activities in support of fusion energy development include the stress analysis and development of design criteria for the first wall of the International Thermonuclear Experimental Reactor (ITER), the computer analysis of tritium breeding and transport in the ITER blanket, and analyses of plasma-first wall interactions in fusion reactors. Stress analysis work is also being carried out on ceramic components to be used in proposed designs for the sodium heat engine and the solid oxide fuel cell. In the fabrication area, a program on the fabrication of nuclear fuel for the Reduced Enrichment Research and Test Reactor (RETR) has been completed, and fuel development and fabrication for the ANS is continuing. Experimental work is also being conducted in support of fuel fabrication and reprocessing for the IFR. In addition, a target source for ANL's Intense Pulsed Neutron Source (IPNS) facility is being fabricated.

¹Special Term Appointee.

LWR Mechanical Testing and Component Examination

Environmentally Assisted Cracking in LWRs

Studies on the environmentally assisted cracking of piping and pressure vessels in LWRs are being conducted under an ongoing program sponsored by the NRC. These studies are being carried out in both the Mechanics of Materials Section and the Corrosion Section. Those activities being performed in the Mechanics of Materials Section include (1) measurement of crack growth rates in austenitic stainless steel piping materials and ferritic pressure vessel steels in boiling water reactor (BWR) environments, (2) determination of the fatigue behavior of austenitic and ferritic steels in LWR environments, and (3) development of experimental techniques for controlling electrochemical potential in environmental mechanical tests.

Fracture-mechanics crack-growth-rate (CGR) tests have been conducted on Types 304, 316 NG, and 347 stainless steel (SS), as well as on cast duplex SS, over a wide range of environments and loading conditions. Crack growth rates in modified Type 347 SS were comparable to those observed in Type 316NG SS. However, the susceptibility of modified Type 347 SS to environmentally enhanced cracking may be reduced by heat treatment. The crack growth rates in a cast CF-3 duplex SS with 15.6% ferrite content tested in simulated BWR water were an order of magnitude lower than those in a CF-3M with 5% ferrite. The differences in susceptibility observed between the two materials are consistent and support the conclusion that only cast stainless steels with $C < 0.035\%$ and ferrite level $> 8\%$ be considered as highly resistant to cracking. Water chemistry was found to strongly influence the stress corrosion cracking (SCC) susceptibilities of Types 304 and 316 NG SS. Most impurities have been found to be detrimental, but as the studies carried out by the Corrosion Section have shown, additions of certain organic acids have actually been found to be beneficial.

CGR tests have also been conducted on high-sulfur (0.018 wt.%) A533 Grade B ferritic pressure vessel steel. These tests are being performed to determine threshold levels of the stress intensity factor as a function of environmental, material, and loading history variables. The parameters include the dissolved-oxygen concentration, anion and cation impurities, heat-to-heat variations, and metallurgical variables, including inclusion content and cladding with austenitic stainless steel. Emphasis is placed on high-load-ratio (high-R), low-frequency cyclic loading conditions. The objective of the study on SCC of ferritic steels is to better define the environmental, material, and loading conditions that can produce SCC in these steels under conditions relevant to LWR water chemistry environments.

Results obtained from these tests indicate that sustained crack growth in a high-sulfur A533-Gr B steel in an environment with 0.2 ppm dissolved oxygen under loading with an 0.95 load ratio occurred only when stress intensity factors were greater than $30 \text{ MPa}\cdot\text{m}^{1/2}$. Most of the crack growth at this R-ratio occurred as transient bursts. Between these bursts, the local slow crack growth under 0.95 load ratio is in reasonable agreement with the proposed ASME Section XI fatigue growth curves for low alloy steels, but the transient growth rates and overall average crack growth rate greatly exceed the predictions. However, CGRs at other load ratios ranging from 0.25 to 0.9 are in reasonable agreement with the proposed curves. Even at the 0.95 load ratio, the magnitude of the environmental

enhancement observed is relatively consistent with that predicted, but the enhancement is observed at much lower threshold stress intensity levels than predicted.

In addition to conventional specimens, specimens plated with either nickel or gold have been tested. These specimens, which are resistant to surface oxidation, are intended to provide insight into whether electron transfer through the oxide film on the bulk surface of the ferritic steel is an important rate-limiting process, and whether data obtained on specimens without cladding can be used to analyze the behavior of a clad ferritic vessel. Initial results suggest that CGRs in the plated specimens were generally significantly higher than in the conventional specimen, although the actual differences depended upon specific loading conditions. Additional testing is currently underway to further assess the possible effects of the cladding.

Residual-life assessment reviews for LWRs indicate that low-cycle fatigue is a potentially significant degradation mechanism in LWR structural components. This degradation mechanism must be considered when justifying extended operation of an LWR plant. Current fatigue design for austenitic SS piping is based on the ASME Section III fatigue design curves. Environmental effects are not explicitly considered in these curves. Instead, the design curves are obtained by introducing a factor of 2 on the strain range or 20 on the cycles from the mean life curve, whichever is more conservative. These safety factors are intended to account for a number of actors such as surface finish, environmental effects, etc. For strain ranges greater than 0.25%, the fatigue life of Type 316NG SS in oxygenated water environments at 288°C falls well below the mean curve. Only at very low strain rates do any data fall below the design curve, but there is a significant reduction in the margin of safety for lives between 10^4 and 10^6 cycles. However, in the high-cycle regime, the water environment seems to have a beneficial effect on fatigue life and at a strain range of 0.25%, fatigue life in the water environment is more than 7 times that in air.

Studies in the U.S. and Japan have shown that the effect of typical BWR environments on the fatigue life of A106-Gr B and A333-Gr 6 steel can completely erode the "2 or 20" margin in the Code Design Curve. Tests are being performed at ANL on ferritic pressure vessel and piping steels both in air and in high-purity water and simulated PWR water. The objective of this work is to provide additional information on the effects of operating temperature and environment on the fatigue behavior of structural alloys. The data obtained by ANL from the baseline air tests all lie above the ASME design curve. However, at higher strain ranges, the safety factor on cyclic life is found to range from ≈ 3 to 10 rather than the factor of 20 intended by the design curve. Testing in both high-purity water and simulated PWR water is now underway to determine the effect of these environments on fatigue life. Variables such as sulfide inclusion size, shape, and morphology will be addressed.

Initial studies are also underway to control the electrochemical potential of specimens during corrosion-fatigue and CGR tests. We believe that electrochemical-potential control of specimens will be an effective means to simulate dissolved oxygen and other introduced chemical species. The effects of these variables on the properties of pressure boundary alloys in PWR environments can then be investigated by simple potential control rather than through chemical control, which is very difficult in laboratory test systems at the low

dissolved oxygen levels (5–20 ppb) typically present in the PWR environment. The greater degree of control provided by this technique may also be helpful in gaining insight into operative corrosion-enhanced fatigue-crack-growth mechanisms.

Stress Corrosion Cracking of Candidate Waste Canister Alloys

The Nevada Nuclear Waste Storage Investigations Project has been investigating the feasibility of locating a repository for high-level nuclear waste in tuff formations at Yucca Mountain in southern Nevada. The waste forms are to be isolated from the environment by a waste canister. Six metallic materials were initially considered for the canister: Types 304L and 316L stainless steels, Incoloy 825, phosphorus-deoxidized copper (Cu), Cu-30%Ni, and Cu-7%Al. These materials were chosen because of their favorable corrosion properties and extensive experience in marine, nuclear, and process industries. The present program has been initiated to determine whether any of these materials can survive for 300 years in the site environment without developing through-wall stress corrosion cracks, and to assess the relative resistance of these materials to stress corrosion cracking. This work is sponsored by DOE under a subcontract from Lawrence Livermore National Laboratory.

A series of slow-strain-rate tests (SSRTs) in simulated Well J-13 water that is representative of the groundwater present at the Yucca Mountain site have been performed, and CGR tests are also being conducted under the same environmental conditions. Although for much of the time the temperature will be sufficiently high that any water in the vicinity of the canisters will be present only in the form of steam, the tests focus on aqueous environments at 90–95°C, because these conditions are considered to provide the "worst case" for SCC.

The SSRTs showed that virtually all the materials, base and weldments, crack in SSRTs at 93°C and at strain rates of 10^{-7} and 10^{-8} s⁻¹. The ranking of susceptibility to cracking, in order of increasing resistance, was: Type 304L SS < Type 316L SS < Incoloy 825 and Cu-30%Ni < Cu and Cu-7%Al. Fracture-mechanics SCC crack-growth-rate tests on Types 304L and 316L stainless steels and Incoloy 825 showed no evidence of cracking at 0.07 Hz under a stress intensity of 25 MPa·m^{1/2} and a load ratio of 0.9 for 5000 h. This indicates that the average CGRs were less than 2×10^{-12} m·s⁻¹. No evidence of environmentally accelerated crack growth has been observed for Types 304L and 316L stainless steels and Incoloy 825 in CGR tests under varying frequencies of 0.5 to 0.002 Hz at 25 MPa·m^{1/2} and a load ratio of 0.9. These tests are continuing.

TMI-2 Vessel Integrity Program

Extensive studies have been conducted during the past several years to determine the extent of the damage suffered by the TMI-2 nuclear reactor as a result of the loss-of-coolant accident that occurred on March 28, 1979. Despite the fact that approximately 20 metric tons of molten core debris fell onto the bottom of the reactor, the lower head did not fail. The objectives of the present program are to determine a scenario for and deduce the temperatures of the steel in the lower vessel head during the accident, determine the mechanical properties of the steel from the lower head under the core melt accident

conditions, and assess the integrity of the TMI-2 vessel during the accident. The program is sponsored by the NRC and the Organisation for Economic Co-operation and Development (OECD), and the research is being conducted by ANL, the Idaho National Engineering Laboratory (INEL), and participating member countries of the OECD.

Samples of A-533, Grade B steel "archive material" have been obtained from the lower head of the cancelled Midland nuclear reactor, a plant very similar in design and fabrication history to TMI-2. Heat treatment experiments conducted under controlled heating and cooling conditions on this material have produced a set of standard microstructures that can be compared with the microstructures observed in the actual TMI-2 lower head samples. In addition, mechanical test specimens will be fabricated from this archive material and heat treated to simulate the thermal history of the TMI-2 lower head during the accident. These specimens will be used to supplement the mechanical-property data obtained from the limited number of TMI-2 test specimens available. A series of round-robin mechanical tests has been conducted by the participating OECD laboratories on the as-received archive material to confirm that no significant interlaboratory variation is present.

Fifteen samples have been recovered from the TMI-2 lower head and sent to ANL. These prism-shaped samples have a typical length of ≈ 165 mm, a width of ≈ 70 mm, and a depth of ≈ 65 mm. This depth corresponds to approximately one-half the thickness of the TMI-2 lower head. Four of the samples contained penetrations for instrumentation nozzles. With two exceptions, the samples were chemically and mechanically decontaminated, and metallographic specimens were taken through the cross sections.

The TMI-2 lower head samples were cut from the inside surface of the pressure vessel lower head and include the full ≈ 5 – 7 mm thickness of the weld-deposited Type 308L stainless steel cladding. Cracks were observed in this clad surface for two of the as-received lower head samples. A detailed examination of one of these two samples revealed that the surface crack penetrated the cladding, but extended for a distance of only ≈ 3 mm into the underlying A533, Grade B steel base metal, as seen in the micrograph. The cracked region in the base metal was heavily oxidized, and molten control assembly constituents (In-Sn) from the reactor core had penetrated into the oxide cracks. Other molten control constituents, including Ag-Cd globules and phases rich in Ag, In, Cd, and Sn, were detected on the surfaces of the crack exposed to the core. However, only a few small fragments of nuclear fuel were detected, and there was no evidence that molten fuel had interacted with the cladding or entered the crack.

The cracking observed in the cladding is tentatively attributed to hot tearing that occurred during the early stages of cool-down after the molten core materials had contacted the lower head. The still-hot cladding would have been placed into tensile loading at this time because of thermal contraction. Microstructural examination of the lower head base metal adjacent to the crack indicates that it reached a maximum temperature of ≈ 1000 to 1100°C during the accident, and the cladding material was probably somewhat hotter. Examination of the microstructures present in the remaining

Metallographic section through surface region of sample from TMI-2 lower head, showing surface cracking. The crack extends through the unetched stainless steel surface cladding and into an oxidized region of the underlying base metal.

lower head samples is continuing. When these examinations are completed, mechanical test specimens will be cut from the lower head samples and the mechanical properties of the lower head material will be determined over the range of temperatures reached during the accident.

Analysis of Failed Components from Nuclear Power Plants

This activity, which has been carried in the Mechanics of Materials Section for a number of years, is sponsored primarily by Commonwealth Edison Company, although analyses are occasionally performed for other electric utilities. The objectives of the analyses are typically to determine the root cause(s) of failure and to suggest remedial action to avoid similar failures in the future. The analyses commonly include the use of nondestructive, metallographic, and SEM examination, as well as chemical analyses of radioactively contaminated samples.

Mathematical Modeling and Analysis

Integral Fast Reactor Fuel Behavior

Models and properties for advanced metallic fuel alloys (U-Pu-Zr) have been incorporated into the LIFE code for the purpose of analyzing the thermal and mechanical performance of IFR fuel rods under normal operating conditions. The resulting code, LIFE-METAL, has received extensive validation to the large data base for U-Pu-Zr fuels clad in austenitic (D9) steel for heavy metal burnups to 18 at.% and cladding fast fluences to 18×10^{22} nvt. Efforts during the past year have been directed toward validating LIFE-METAL to the evolving data base for the U-19Pu-10Zr alloy clad in ferritic (HT9) steel. This fuel element design (Mark-V) is planned as the next driver fuel for the EBR-II experimental fast reactor. The fission-product swelling and fission-gas release models were improved to give good agreement between LIFE-METAL predictions and the U-19Pu-10Zr/HT9 data base for irradiated fuel elements with a wide range of fabrication conditions: 70-85% fuel smear densities, 1:2 plenum-to-fuel volume ratios, and 6-14 wt.% Zr content. The code was then used to predict the performance of peak-power and peak-cladding-temperature fuel elements in the anticipated Mark-V core loading. Additional studies were performed to determine the sensitivity of fuel thermal performance to uncertainties in material properties. Finally, the performance of the Mark-V fuel element under very low power and high temperatures (800°C) was analyzed (with the analytical results being validated to data from furnace tests).

VICTORIA Code Development

VICTORIA is a computer code being developed by Sandia, Argonne, and Oak Ridge National Laboratories under NRC sponsorship, as well as by Chalk River Nuclear Laboratories (Canada) and the Winfreth Technology Centre (UK). The code will calculate fission product release and transport within LWR coolant systems and is a new version of the code originally generated at Sandia. Modeling of the release of radionuclides from reactor fuel and the subsequent behavior of these species is an essential aspect of severe reactor accident analysis. ANL's primary responsibility is to provide the modeling of fission product release from fuel during the severe fuel damage accident phases of rubble bed formation, heating, melting, and quenching. ANL has completely reworked the code structure to provide computational efficiency and a basis for VICTORIA validation, i.e., verifying that the models and solution procedures described in the user manual are indeed in the code and are being implemented correctly. Near-term work has focused on the implementation of fission-product transport models through intact fuel and from fuel morphologies ranging from just beyond intact rods (i.e., fuel liquefaction and partial dissolution). The intragranular diffusive flow calculation is based on a two-node model that agrees very well with a detailed finite-element calculation. In addition, a calculation for gas-bubble behavior on grain boundaries was implemented, a calculation that is required in order to compute intragranular porosity interconnection (IPI). Currently, IPI is an input quantity in VICTORIA and does not change through the course of a run. A realistic kinetic prediction of fission product release to the fuel-clad gap, or the bulk gas in the event of cladding failure, is strongly dependent on an accurate calculation of IPI.

Advanced Neutron Source

Development of the design for a new high-flux research and test reactor, i.e., the Advanced Neutron Source (ANS) is in progress at Oak Ridge National Laboratory. The Section is modeling the behavior of proposed fuels for this reactor. Recent experimental observations on low-temperature swelling of irradiated uranium silicide dispersion fuels have indicated that the growth of fission gas bubbles appears to be affected by fission rate. The swelling curve of the material exhibits a distinct "knee" that shifts to higher fission density with increased rate due to higher enrichments. Current state-of-the-art models for fission gas behavior do not predict such a dependence. Grain subdivision, which has been observed in high-burnup uranium oxide, has been proposed as a possible mechanism for this phenomenon wherein a dense network of grain boundaries forms in uranium silicide at a dose corresponding to the "knee" in the swelling curve; fission gas bubbles nucleate at the boundaries and then grow at an accelerated rate relative to those in the bulk material. A theoretical formulation was developed wherein the stored energy in the material is concentrated in a network of recrystallization sites that diminish with dose due to interaction with radiation-produced defects (vacancy-solute pairs). Recrystallization is induced by statistical fluctuations when the energy per site is high enough so that the creation of grain-boundary surfaces is offset by the creation of strain-free volumes, with a resultant net decrease in the free energy of the material. This formulation was shown to provide a qualitative interpretation of the observations in both the intermetallic and the oxide material. Other possible mechanisms (e.g., phase changes) are currently under investigation.

ITER Stress Analysis and Design Criteria

Support is being provided for the U.S. design effort for the International Thermonuclear Experimental Reactor (ITER). This support is in the areas of stress analysis of the blanket and divertor, as well as in the development of structural design criteria. A serious problem facing the ITER blanket and first wall is the high primary bending stress due to electromagnetic pressure loading during plasma disruptions. These pressure loadings are fast transients acting over times of the order of milliseconds; in some scenarios, however, peak pressures as high as 1 MPa are imposed on the first wall. Much of the design activity during the past year has centered on devising ways to keep the maximum primary stress within the allowable limit by providing adequate stiffness and support for the first wall. However, the problem is exacerbated by the fact that the first wall is also subjected to high cyclic thermal stresses due to plasma on-off cycles. This makes it impossible to keep the maximum stresses in the first wall from exceeding the yield limit, and it also creates a potential deformation problem because of ratcheting. Because the ASME Boiler and Pressure Vessel Code design criteria to deal with ratcheting are not strictly applicable to the ITER geometry and loading, new design criteria are being developed.

Analysis of Plasma/First Wall Interactions

Modeling and analyses are being performed on the effects of plasma disruption on both the divertor plate/wall coating and on the substrate structure. This problem continues to be a major issue with respect to the feasibility and successful operation of a magnetically confined fusion reactor. The high energy deposition during a disruption can cause severe erosion of the coating material through melting and vaporization of the surface.

One major uncertainty currently being studied is the so-called vapor shielding effect. This occurs when the vaporized surface material from the first wall interacts with the incoming plasma ions and reduces further deposition of energy on the wall. This shielding effect can substantially reduce the erosion and consequently prolong reactor component lifetimes.

Another important problem occurs in modeling the erosion from the melt layer formed on the surface of the divertor/wall metallic material as a result of plasma disruption. This modeling involves the solution of hydrodynamic equations for the melt layer subject to the various forces that are present during the course of the disruption.

Another plasma/wall interaction being analyzed is the sweeping of the heat load on the divertor surface at varying frequencies to reduce both the heat load on the surface and the critical burnout heat flux at the coolant channels.

Tritium Breeding and Transport

The Tritium Inventory and Release Analysis (TIARA) code has been developed to perform purge flow hydraulics/chemistry and tritium retention/release analyses for fusion solid breeder ceramics under steady-state operating conditions. The primary focus of recent activity has been on the ceramic Li_2O because of its importance in the conceptual designs for the tritium breeding blanket of the ITER and because of its well-developed data base. Paralleling the TIARA development effort is the development of a code to perform transient tritium transport calculations under the anticipated ITER pulsed operation. Modifications were made to the ANL code DISPL2 for this purpose. The results of both steady-state and transient calculations were documented in the U.S. contribution to the ITER final report for the conceptual design phase. In future modeling efforts, other promising ceramics (e.g., LiAlO_2 and Li_2ZrO_3) will be considered.

Also included in this research effort is the modeling and coordination of all experimental work in the U.S. program to characterize the tritium retention/release and helium-induced swelling in the Be multiplier material of the proposed ITER blanket. It is anticipated that more than 1 kg of tritium will be generated in the 100–200 metric tons of Be. Swelling is important because the thermal and mechanical performance of the blanket is very sensitive to the swelling of Be. Significant progress has been made during this past year in developing a data base in these areas and in modeling tritium and He behavior. Additional experiments and modeling efforts are underway to study the sensitivity of tritium and helium behavior to as-fabricated porosity and oxygen impurity levels.

As a third part of this effort, the Section assumed the lead role in the development of a material-property data base and a set of property correlations to be used by all ITER designers. The final document, published in the spring of 1991, includes material properties for nuclear, thermal, mechanical, tritium, irradiation, and chemical performance of tritium breeder materials (Li_2O , Li_4SiO_4 , Li_2ZrO_3 , LiAlO_2 , and Pb-Li) and neutron multiplier material (Be). This document is being used by all of the design teams in their contributions to the ITER final report for the conceptual design phase.

Sodium Heat Engine

The sodium heat engine, currently being developed under the auspices of DOE, employs β " solid electrolytes. Although the basic physics of the heat engine is well understood, an impediment to the successful commercialization of the system has been the premature cracking of the β " alumina tubes. The Mechanics of Materials Section, together with the Ceramics and NDE Sections of MCT, is currently involved in identifying the sources of the problem and developing solutions by means of detailed analyses of the stresses in the tube as well as by improving their fracture strength. The absorption of neutral sodium by β " alumina has been reported as a possible source for high stress, because it causes a large anisotropic strain in the c-axis direction of the β " alumina grains. A preliminary stress analysis has shown that the large anisotropic strain could lead to high internal residual stresses and cause cracking. Detailed stress and fracture mechanics analyses for pursuing this hypothesis are planned for this fiscal year.

Solid Oxide Fuel Cell

The solid oxide fuel cell, which was originally conceived at ANL under a program sponsored by the Defense Advanced Research Projects Agency, is currently being further developed for future commercialization by Allied Signal, Los Angeles Division, under the auspices of DOE. ANL is a subcontractor to Allied Signal to provide support in the area of developing a stress analysis model for the fuel cell stack. The fuel cell is a honeycomb structure consisting of four layers: cathode, electrolyte, anode, and interconnect. The challenge is to successfully cofire the entire stack and cool it down to room temperature without cracking. A thermal stress model for analyzing the stresses developed during cool-down after sintering has already been developed. Based on this model, minimum fracture strengths necessary for the various layers have been derived. A model for analyzing stresses developed during sintering is currently being developed. In addition to providing target fracture strengths for the basic materials, the analyses will eventually help Allied Signal to develop a finite-element model for analyzing stresses in the entire stack, including manifolds, during fabrication and subsequent operation.

Fabrication and Nuclear Fuel Reprocessing

Integral Fast Reactor*

As part of the IFR program, a Fuel Cycle Demonstration is focused on processing spent irradiated fuel elements to recover U and Pu for future fuel inventory. Fissile material recovery by electrorefining yields a porous cathode product contaminated with Cd and an LiCl/KCl mixture. A cathode processor is planned to remove the contaminants and consolidate the fissile material. A Cathode Processor Simulation Experiment (CPSE) has been devised to support the reference design activity and to evaluate process viability. This experiment focuses on:

- Removal of contaminants from the cathode dendrite stock by vaporization and condensation.
- Consolidation of the metallic dendrites to produce a solid ingot.
- Process optimization to produce a high-quality fissile product with minimum losses.

An experimental assembly was designed to operate within the environment of a vacuum induction furnace. Contaminant removal was verified for the Cd and LiCl/KCl species. Process development has focused on the use of electrorefined dendrites from the solid cathode source. On achieving an acceptable level of viability on charges at the 1-kg level, process modification involving the use of upscaled charges was successfully demonstrated in late 1990. Process demonstration on a full-scale quantity of dendrites with a 7.9-kg charge yielded a 7.1-kg ingot. This static casting (shown in the photograph) is a well-formed ingot with sound internal structure. Chemistry monitoring indicates that typical contaminants in the dendrite stock give wt.% values of Cd 0.02–0.40, Li 0.53–0.97, K 1.9–3.6, Cl>2.0, which compare with refined-ingot ppm levels of Cd<2, Li<2, K<50, Cl<15. The CPSE experiment has demonstrated efficient removal of the contaminants Cd, Li, K, and Cl from the dendrite feedstock, as well as consolidation of the metallic residues into a high-quality casting. This achievement demonstrates the viability of the cathode processor concept.

Reduced-Enrichment Research and Test Reactor

The RERTR program is being conducted in support of the nuclear nonproliferation policies of the federal government. ANL contributions to this international program were recognized with an IER 100 Award in 1985 and an Excellence in Technology Transfer Award in 1986. A keystone of this program is the development and utilization of low-enrichment, high-density, uranium-bearing fuels for use as dispersed-phase powders in plate-type elements. At a typical enrichment of $19.7 \pm 0.2\%$, the diversion of the fuel alloy from fabrication facilities or reactors—before or after irradiation—to weapons use is precluded. More than 200 aluminum-alloy-clad "miniplates" were fabricated in our facilities and irradiated in the Oak Ridge Research Reactor.

Static casting of U-1.5 wt.% Zr alloy with yield of 7.1 kg

From several candidate fuels used in the ANL fabrication effort, the irradiation performance of U_3Si_2 has been demonstrated as very good up to high fuel burnup. Through ANL technology transfer, U_3Si_2 is now a commercially available fuel for core conversions. The NRC issued NUREG-1313 in the summer of 1988, concluding that U_3Si_2 dispersed in Al with U densities up to 4.8 g/cm^3 is acceptable for use in licensed nonpower reactors.

The Section is now focusing its activities in three major areas:

- A continuation of technology transfer with domestic and foreign fabricators to enhance their knowledge of U_3Si_2 and their abilities to fabricate plate-type elements with this fuel. A recent activity in this area was the exchange of technology with the United Kingdom Atomic Energy Authority, Dounreay, Scotland.
- A report summarizing the last 12 years of uranium-silicide fuel plate fabrication at ANL has been written and is in the editing stage. This report also briefly reviews related subjects on all aspects of the program and will serve as a central document for future reference.
- The supply of fuel powders, hardware, and technical support for use by ANL's Materials Science Division for fundamental studies of the behavior of U_3Si_2 and U_3Si under ion and/or neutron irradiation.

Advanced Neutron Source Reactor

In addition to the fuel modeling work described above, the Section is also involved in development and fabrication of fuels for the ANS. This reactor concept requires a fuel that will operate satisfactorily at temperatures and neutron flux levels never before encountered.

To date, 18 "fuel holders" have been fabricated and irradiated in the Oak Ridge High Flux Isotope Reactor; they are now cooling poolside before undergoing post-irradiation examination (PIE). A second set of 18 fuel holders has been produced and is ready for final machining when the PIE results of the first set are evaluated. Two additional sets of 18 holders are planned for fabrication for the current fiscal year. Fuels incorporated into the test matrix include U_3Si , U_3Si_2 , UAl_x , UAl_2 , and U_3O_8 .

In concert with work by Babcock & Wilcox (Lynchburg, VA), fabrication and inspection techniques are being examined and tested to produce fuel plates with controlled fuel gradients across both the width and the length of a fuel plate. Fundamental studies of fuel powder characteristics and their relationship to uniformity of the fuel plate loading are planned. Also, modified compacting techniques will be made to study the reproducibility of fabricating these complex graded fuel loadings. With the addition of a specified fuel gradient, the measurement of fuel loading variation is not a simple deviation from constant loading but a deviation from a linear function. A greater amount of data must be collected to fully characterize the loading of these fuel plates. Digitizing the loading level information for computer processing is the most expeditious method to analyze the data. To analyze the fuel plate loading, two techniques are being used — line scans from the B&W X-ray attenuation scanner and standard X-ray films of the fuel plates. Effort will be focused on digitizing the output of the B&W X-ray attenuation fuel plate scanner. In addition, methods are being developed to digitize the standard X-ray films and perform digital image processing and analysis on these films.

Target Source for Intense Pulsed Neutron Source Facility

In previous years, the section produced neutron decoupling inserts that were a critical safety requirement for the IPNS upgrade. The inserts were made by a powder metallurgy process and consisted of ^{10}B and Cu powder clad with pure Cu. In 1989, approval was given to produce backup neutron decoupler inserts for the target housing assembly of the IPNS. Fabrication of this hardware began in 1990 and was nearing completion in late 1990. A statutory invention registration was issued by the U.S. Patent Office for this material in September 1990.

Recent Work by the Mechanics of Materials Section

Publications

Mechanical Properties and Deformation of Polycrystalline Lithium Orthosilicate

K. Bär (Institute of Reactor Materials, Germany), C. Y. Chu (Illinois Institute of Technology), K. C. Goretti, J. L. Routbort, M. C. Billone, and R. B. Poeppel
Fusion Engineering and Design 8, 371-374, (1989) North-Holland, Amsterdam.

Mechanical Performance of Fusion Solid Breeder and Multiplier Materials

M. C. Billone and W. T. Grayhack

Fusion Technol. 15, Number 2, Part 2A and 2B, 876-880 (March 1989). (Proc. 8th Topical Mtg. on of Fusion Energy, Salt Lake City, UT, Oct. 9-13, 1988.)

Models for Calculating Steady-State Inventory

M. C. Billone

To be published in Proc. 2nd Specialists Workshop on *Modeling Tritium Behavior in Ceramic Fusion Blankets*, Indianapolis, IN, April 27-28, 1989, International Energy Agency (IEA), June 1989, pp. 135-174.

Tritium and Helium Behavior in Irradiated Beryllium

M. C. Billone, H. Attaya, Y. Gohar, and C. C. Lin

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Tritium Retention and Release Analysis for the U.S. -ITER Driver Blanket

M. C. Billone, C. C. Lin, and D. L. Baldwin (Pacific Northwest Laboratory)

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, (Poster Paper) Oct. 7-11, 1990.

Thermomechanical Analysis of the U.S.-Iter Driver Blanket

M. C. Billone and S. Majumdar

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, (Poster Paper) Oct. 7-11, 1990.

Tritium Retention and Research Analysis for the U.S. ITER Driver Blanket

M. C. Billone, C. C. Lin, H. Attaya, and Y. Gohar

To be published in Proc. of 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Tritium and Helium Behavior in Irradiated Beryllium

M. C. Billone, C. C. Lin, and D. L. Baldwin (Pacific Northwest Laboratories)

To be published in Proc. of 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Thermal Annealing of Solid Kr Precipitates in Ni

R. C. Birtcher, J. Rest, and D. S. Bergstrom

Submitted to MRS 1989 Fall Mtg., Symp. A, *Beam-Solid Interactions: Physical Phenomena*, Boston, MA, November 27- December 2, 1989.**Irradiation Embrittlement of the Shippingport Neutron Shield Tank**

O. K. Chopra and W. J. Shack

Presented at 15th MPa Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.**Irradiation Embrittlement of the Shippingport Neutron Shield Tank**

O. K. Chopra and W. J. Shack

To be published in Proc. 15th MPa-Seminar on *Safety and Reliability of Plant Technology*, Stuttgart, FRG, October 5-6, 1989.**Embrittlement of the Shippingport Reactor Shield Tank**

O. K. Chopra and W. J. Shack

To be presented at the 17th *Water Reactor Safety* Information Mtg., Rockville, MD, October 23-25, 1989.**Embrittlement of the Shippingport Reactor Neutron Shield Tank**

O. K. Chopra, S. T. Rosinski (Sandia National Laboratories), and W. J. Shack

Presented at the 1990 ASME *Pressure Vessels and Piping* Conf., Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990.**Embrittlement of the Shippingport Reactor Neutron Shield Tank**

O. K. Chopra, S. T. Rosinski (Sandia National Laboratories), and W. J. Shack

Fatigue, Degradation, and Fractures, ed. W. H. Bamford, C. Becht IV, S. B. Framatome, J. D. Gilman, L. A. James, and M. Prager. (Proc. 1990 ASME *Pressure Vessels and Piping* Conf., Symp on *Degradation of Ferritic, Austenitic and Duplex Stainless Alloys in Nuclear Service*, Nashville, TN, June 17-21, 1990), The American Society of Mechanical Engineers, New York, NY (1990), PVP-Vol. 195, pp. 157-168.**Mechanical Properties of Polycrystalline Lithium Orthosilicate**

C. Y. Chu (Illinois Institute of Technology), K. Bär (Institute for Reactor Materials, FRG),

J. P. Singh, K. C. Goretti, M. C. Billone, R. B. Poeppel, and J. L. Routbort

INVITED PAPER published in J. Am. Ceram. Soc. 72(9), 1643- 1648 (1989).

Relationship between Fabrication Parameters and Structural Characteristics of Sintered Lithium Orthosilicate

C. Y. Chu (Illinois Institute of Technology), K. Bär (Institute of Reactor Materials, FRG),

J. P. Singh, R. B. Poeppel, and M. C. Billone

Fusion Engineering and Design 8, 375-378, (1989) North-Holland, Amsterdam.

Predicted Irradiation Behavior of U_3O_8 -AL Dispersion Fuels for Production Reactor Applications

A. W. Cronenbert (Engineering Science and Analysis), J. Rest, M. L. Hyder, Westinghouse Savannah River Co.), J. P. Morin (WSRC), and H. P. Peacock (WSRC)
To be presented at ANS International Topical Meeting on *Safety of Non-Commercial Reactors and Irradiation Facilities*, Boise, ID, Sept. 30 - Oct. 4, 1990.

TMI-2 Vessel Investigation Project (VIP) Metallurgical Program

D. R. Diercks
ANL-90/2, NUREG/CR-5224, Vol. I (February 1990)

TMI-2 Vessel Investigation Project (VIP) Metallurgical Program

D. R. Diercks (Prepared for U.S. Nuclear Regulatory Commission)
Progress Report, January-September, 1989, NUREG/CR-5224; ANL-90/2, Vol 1.

TMI-2 Vessel Investigation Project (VIP) Metallurgical Program

D. R. Diercks and L. A. Neimark
To be presented at the 18th *Water Reactor Safety*, Information Mtg., Rockville, MD, October 22-24, 1990.

Design Description for the Tritium Recovery System for the U.S. Li_2O/BE Blanket for ITER
P. A. Finn, M. Billone, Y. Gohar, D. K. Sze, R. Clemmer (Battelle Pacific Northwest Laboratory), and L. Greenwood (Battelle Pacific NW Lab.)

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

U. S. Solid Breeder Blanket Design for ITER

Y. Gohar, H. Attaya, M. Billone, C. Lin, C. Johnson, S. Majumdar, D. Smith, B. Nelson (Oak Ridge National Laboratory), D. Williamson (ORNL), C. Baker (ORNL), P. Goranson (ORNL), A. Raffray (University of California), A. Badawi (UC), Z. Gorgis (UC), A. Ying (UC), M. Adhou (UC), I. Sviatoslavsky (University of Wisconsin-Madison), J. Blanchard (UWM), E. Mogahed (UWM), M. Sawan (UWM), and G. Kulcinski (UWM)

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Neutronics and Thermal Design Analyses of U.S. Solid Breeder Blanket for ITER

Y. Gohar, M. Billone, H. Attaya, and M. Sawan (University of Wisconsin-Madison)
Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, (Poster Paper) Oct. 7-11, 1990.

Neutronics and Thermal Design Analyses of U.S. Solid Breeder Blanket for ITER

Y. Gohar, M. Billone, H. Attaya, and M. Sawan (University of Wisconsin-Madison)
To be published in Proc. of 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

U.S. Solid Breeder Blanket Design for ITER

Y. Gohar, H. Attaya, M. Billone, C. Lin, C. Johnson, S. Majumdar, D. Smith, P. Goranson (Oak Ridge National Laboratory), B. Nelson (ORNL), D. Williamson (ORNL), C. Baker (ORNL), I. Sviatoslavsky (University of Wisconsin-Madison), J. Blanchard (UWM), E. Mogahed (UWM), M. Sawan (UWM), and G. Kulcinski (UWM)

To be published in Proc. of 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Environmentally Assisted Cracking in Light Water Reactors

T. F. Kassner, J. Y. Park, W. E. Ruther, and W. J. Shack

To be published in Proc. 17th *Water Reactor Safety* Information Mtg., Rockville, MD, October 23-25, 1989.

Environmentally Assisted Cracking of Austenitic and Ferritic Steels in Simulated BWR Water

T. F. Kassner, J. Y. Park, W. E. Ruther, W. K. Soppet, and W. J. Shack

INVITED PAPER to be published in Nucl. Eng. Des.

Neutron Diffraction NDE for Advanced Composites

D. S. Kupperman, S. Majumdar, and J. P. Singh

Trans. ASME 112, 198-201 (April 1990).

Application of Neutron Diffraction NDE to High-Temperature Superconducting Composites

D. S. Kupperman, S. P. Singh, S. Majumdar, A. C. Raptis, and R. L. Hitterman (MSD)

To be published in *Review of Progress in Quantitative NDE*, Brunswick, ME, July 23-28, 1989.

Use of Neutron Diffraction in Determining Strains in High-Temperature Superconducting Composites

D. S. Kupperman, J. P. Singh, S. Majumdar, R. L. Hitterman (MSD), and J. Faber, Jr. (Amoco Research).

Proc. 1989 Fall Materials Research Society Symp., Boston, MA, Vol 166, pp. 195-201 (1990).

Plastic Strain, Environmental, and Crevice Effects on SCC Initiation and Propagation in Types 316NG and 304 Stainless Steel

P. S. Maiya

Corros. 45(11), 915-924 (November 1989).

A Review of Degradation Behavior of Container Materials for Disposal of High-Level Nuclear Waste in Tuff and Alternative Repository Environments

P. S. Maiya

ANL-89/14 (June 1989).

Stress Corrosion Cracking of Candidate Materials for Nuclear Waste Containers

P. S. Maiya, W. J. Shack, and T. F. Kassner

INVITED PAPER: *Corrosion 90* (Proc. High Temperature Symp., Las Vegas, NV, April 23-27, 1990, National Association of Corrosion Engineers, Houston, TX, (1990), pp. 284/1-284/15.

Effects of Composition and Microstructure on Transgranular Stress Corrosion Cracking in Austenitic Stainless Steels

P. S. Matya

J. Mater., 90 (November 1989).

Stress-Related Problems in Tokamak Fusion Reactor First Walls

Saurin Majumdar and Bipin Pai (Purdue University)

Fusion Technol. 15, 1560-1570 (July 1989).

Residual Thermal Stresses and Strains in a WC-Base Cemented Carbide Composite

S. Majumdar

Mater. Sci. Eng. A123, L1-L3 (1990).

Environmentally Assisted Cracking In Light Water Reactors

J. Y. Park, W. E. Ruther, T. F. Kassner, and W. J. Shack

To be published in Proc. 18th *Water Reactor Safety* Information Mtg., Rockville, MD, October 22-24, 1990.

Steady State Deformation of Some Lithium Ceramics

R. B. Poeppel, M. C. Billone, D. S. Applegate, E. Buchmann, B. Lonschien, and J. L. Routbort

Advances in Ceramics 25, 175-181, American Ceramic Society, Inc., *Fabrication and Properties of Lithium Ceramics*.

Modeling Studies on the Precipitation of Krypton after Implantation into Metals

J. Rest, R. C. Birtcher, and A. S. Liu

Proc. 14th Intl. Symp. on *Effects of Radiation on Materials*, Andover, MA, June 27-29, 1988, ed. H. Packan, R. E. Stoller, and A. S. Kumar, Vol II, ASTM STP 1046, American Society for Testing and Materials, Philadelphia, PA, 1990, pp. 353-363.

Precipitation Kinetics of Rare Gases Implanted into Metals

J. Rest and R. C. Birtcher

J. Nucl. Mater. 168, 312-325 (1989).

The Effect of Crystal Structure Stability on Swelling in Intermetallic Uranium Compounds

J. Rest, G. L. Hofman, and R. C. Birtcher

Proc. 14th Intl. Symp. on *Effects of Radiation on Materials*, Andover, MA, June 27-29, 1988, ed. H. Packan, R. E. Stoller, and A. S. Kumar, Vol. II, ASTM STP 1046, American Society for Testing and Materials, Philadelphia, PA, 1990, pp. 789-811.

Validation of Mechanistic Models for Gas Precipitation in Solids during Postirradiation Annealing Experiments

J. Rest

J. Nucl. Mater. 168, 243-261 (1989).

Mechanistic Interpretation of an Observed Rate Dependence of Low-Temperature Swelling of Irradiated Uranium Silicide Dispersion Fuels

J. Rest and G. L. Hofman

To be published in Proc. 15th Symp. on *Effects of Radiation on Materials*, Nashville, TN, June 17-21, 1990.

Kinetics of Recrystallization and Fission-Gas Induced Swelling in High-Burnup UO_2 and U_3Si_2 Nuclear Fuels

J. Rest and G. L. Hofman

INVITED PAPER to be published in Proc. NATO Advanced Research Workshop on *Fundamental Aspects of Inert Gases in Solids*, Bonas, France, Sept. 16-22, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, and R. L. Hitterman

To be presented at the Intl. Conf. on *Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, R. L. Hitterman (MSD), and D. W. Schroeder

INVITED PAPER to be published in Proc. Intl. Conf. on *Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

ITER Tritium Breeding Blanket

D. L. Smith, Y. Gohar, and M. Billone

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Mechanical Design and Fabrication of the U.S. Solid Breeder Blanket for ITER

I. N. Sviatoslavsky (University of Wisconsin-Madison), J. P. Blanchard (UWM), Y. Gohar, and S. Majumdar

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

Aries-I Tritium System

D. K. Sze, S. W. Tam, M. Billone, R. Martin (Oak Ridge National Laboratory), and the ARIES team

Presented at 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, (Poster Paper) Oct. 7-11, 1990.

Aries-I Tritium System

D. K. Sze, S. W. Tam, M. C. Billone, A. M. Hassanein, R. Martin (Oak Ridge National Laboratory), and the ARIES Team

To be published in Proc. of 9th Topical Mtg. on the *Technology of Fusion Energy*, Oak Brook, IL, Oct. 7-11, 1990.

A Li-Particulate Blanket Concept for ITER

C. P. C. Wong (General Atomics), E. T. Cheng (Gen. At.), R. L. Creedon (Gen. At.), K. R. Schultz (Gen. At.), G. Thurston (Gen. At.), Y. Gohar (AP), C. Baker (FPP), H. Attaya, M. Billone, A. Hassanein, C. Johnson (CMT), S. Majumdar, R. Mattas (FPP), D. Smith (FPP), and D-K. Sze (CMT)

Fusion Technol. 15, Number 2, Part 2A and 2B, 876-880 (March 1989). (Proc. 8th Topical Mtg. on Fusion Energy, Salt Lake City, UT, Oct. 9-13, 1988.)

Patents**High Loading Uranium Density Fuel Plate**

T. Wiencek, R. F. Domagala, and H. R. Thresh

U.S. Patent No. 4,963,317 awarded December 14, 1990.

Tribology

Section Manager: F. A. Nichols

Assistant Manager: A. I. Michaels

Principal Investigators: G. R. Fenske, A. Erdemir, R. Erck

Support Staff: D. E. Busch

Technician: R. H. Lee

Secretary: D. K. Moores

Postdoctoral Appointees: J. H. Hsieh, O. O. Ajayi

Student: A. Alp¹

The Tribology Section conducts research and development on low-friction and wear-resistant surface coatings and treatments applied to ceramic and high-temperature metal substrates, for use under high load at high temperatures in aggressive chemical atmospheres. These coatings are primarily intended to protect engine component surfaces undergoing sliding and rolling contact in low-heat-rejection diesels and other advanced engines being developed under the sponsorship of the DOE Office of Transportation Technologies. In addition, the Section provides technical direction and administrative support to the DOE Office of Transportation Materials within the Office of Transportation Technologies.

Engineered Tribological Interfaces

This project is exploring the factors that control the tribological properties of surfaces and is attempting to develop high-temperature, low-friction, wear-resistant surfaces by the application of coatings and/or surface-modifying treatments such as ion implantation. Program emphasis is on developing low-friction, high-wear coatings on ceramic and other materials intended for utilization in components for low-heat-rejection diesels and other high-temperature advanced engines and engine power trains. Research is carried out in three major areas: (1) development of low-friction and low-wear surfaces by a variety of methods, including ion-beam-assisted deposition (IBAD), ion-beam mixing (IBM), and ion implantation and other surface treatments; (2) development of ultrahard, low-friction diamond, diamondlike, and other similar coatings by plasma-assisted chemical vapor deposition (PACVD); and (3) tribological testing and characterization of surfaces before and after modification and coating.

¹ Illinois Institute of Technology.

*Schematic drawing of ion-beam-assisted deposition process (top),
and view of interior of ion-beam-assisted deposition
apparatus in operation (bottom)*

Ion-Beam-Assisted Deposition and Ion-Beam Mixing of Coatings

The Tribology Section has designed and constructed a sophisticated and versatile facility for the ion-beam-assisted deposition of low-friction, low-wear coatings. This facility consists of a large, ultrahigh-vacuum chamber with two individually controlled electron-beam evaporation sources and simultaneous or sequential ion sources that produce ions with energies from a few eV to a maximum of 1500 eV. A six-degree-of-freedom specimen manipulator, including rotational motion, is used to ensure uniformity in coating complex-shape substrates and is capable of supporting and manipulating complex engine components such as piston rings and liners. This facility is also utilized for ion-beam mixing of previously deposited multilayer coatings. In addition, the Section has a large commercial sputtering apparatus for the preparation of thick multilayer coatings for direct use or for ion-mixing experiments.

Accomplishments to date include

- Development of silver coatings on alumina, zirconia, and silicon nitride ceramic substrates, which reduced the wear rates by factors of 10 to 3500, depending on load, temperature, velocity, and substrate. Friction was also reduced by one-half to one-third, depending on temperature, for temperatures up to 400°C.
- Deposition of boron oxide coatings on superalloys and ceramics, which virtually eliminate all measurable wear and provide extremely low (< 0.05) coefficients of friction over a wide range of loads and at temperatures up to 200°C. The mechanism involved in these coatings is the formation of boric acid in the presence of atmospheric moisture. Boric acid is a layered-structure material with a very low coefficient of friction and is similar to the solid lubricant molybdenum disulfide.
- Ion-beam mixing of multilayer, alternating iron and boron coatings, which have been successfully produced and shown to reduce friction and to provide a significant decrease in wear rates.

Plasma-Assisted Chemical Vapor Deposition of Diamond and Diamondlike Coatings

The Tribology Section has recently procured a Microwave Plasma Deposition Source from Applied Science and Technology, Inc. This equipment will provide us with the means for producing diamond and diamondlike and similar ultrahard coatings on ceramics and other high-temperature materials. It is expected to be in operation in the early spring of 1991. In the interim, the Section has been evaluating diamondlike coatings produced for us by Colorado State University, which is currently developing a wide-angle, high-density, high-flux metal-ion source under subcontract to ANL. Preliminary evaluation of these diamondlike coatings has been very promising. Limited measurements indicate extremely low coefficients of friction and wear rates.

Tribological Testing and Surface Characterization

In support of its coating and surface-modification research, the Section has developed extensive state-of-the-art facilities for tribological evaluation and surface characterization. Tribological equipment presently used includes high-temperature (up to 900°C) reciprocating pin-on-flat and rotational pin-on-disc friction and wear test machines; a low-temperature, controlled-environment pin-on-disc machine; a high-resolution surface profilometer; and an adhesion-force tester. Computerized control and digitized, computerized data acquisition is used extensively with these test facilities. Design, parts procurement, and construction of a combined high-frequency oscillating friction and wear and scratch-adhesion tester is underway.

Surface characterization equipment includes a state-of-the-art JEOL 840A scanning electron microscope with built-in energy- and wavelength-dispersive X-ray analysis, and an ultramicrohardness tester for in-situ measurements of the hardness of extremely thin films. In addition, the Section has access to other surface characterization facilities in the MCT and Materials Science Divisions.

Program Support to DOE Office of Transportation Materials

The Technical Direction and Administrative Program Support project conducts R&D planning; provides project management services required to implement the R&D program; and monitors, evaluates, and provides guidance for contractors funded by the project. Efforts in the past year included preparation of the Annual Operating Plan and Annual Budget; organization and conduct of the DOE/OTM Guidance and Evaluation Panel Contractor's Review Meeting; and organization and conduct of project review meetings in the areas of Engineered Tribological Interfaces, Extreme Environment Lubrication, and Tribology by Design, the three task areas within the tribology program. In addition, extensive technology transfer activities were conducted throughout the year, including the organization of three sessions containing 16 papers at the Annual Joint ASME/STLE Tribology Conference in Toronto in October 1990.

Measured friction coefficients for uncoated and silver-coated silicon nitrate substrates, with and without lubricant. Uncoated silicon nitrate pins were used on coated and uncoated silicon nitrate flats, at 0.05 m/s, under a normal load of 10 N, which produced a mean Hertzian stress of 150 Mpa.

Recent Work by the Tribology Section

Publications

Investigation of Tribological Properties of Hard Coatings for Cutting Tools

B. P. Bandyopadhyay (University of North Dakota), E. Fabiszak (Micro Surface Corp.), G. R. Fenske, and F. A. Nichols

To be presented at the Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Wear Reduction in Cutting Tools: Tribological Properties of Hard Coatings

B. P. Bandyopadhyay (University of North Dakota), E. Fabiszak (Micro Surface Corp.), G. R. Fenske, and F. A. Nichols

To be published in Proc. Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Investigation of Tribological Properties of Hard Coatings for Cutting Tools

B. P. Bandyopadhyay (University of North Dakota), E. Fabiszak (Micro Surface Corp.), G. R. Fenske, and F. A. Nichols

To be presented at the Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Characterization of IAD and Sputter-Deposited Carbon Films

Cheng, C. C.

TRIB-ECUT-89/3 (July 1990), pp. 94-95.

Characterization of IBAD and Sputter-Deposited Carbon Films

Cheng, C. C.

TRIB-ECUT-89/4 (October 1990), pp. 91-92.

Applications of Ion-Beam Processes in Tribology

R. A. Erck, G. R. Fenske, A. Erdemir, and F. A. Nichols

Proc. 5th Intl. Congress on *Tribology*, Helsinki, Finland, June 12-15, 1989, ed.

Kenneth Holmberg and Ilkka Nieminen, The Finnish Society for Tribology, Espoo, Finland, Vol. 2, (1989), pp. 102-109.

Chi-Phase Precipitation in Ion-Irradiated Molybdenum-Rhenium Alloys

R. A. Erck and L. E. Rehn

Philosophical Magazine A, 62 (1), 29-51 (1990).

Kinetics of Radiation-Induced Segregation in Molybdenum-Rhenium Alloys

R. A. Erck and L. E. Rehn

J. Nucl. Mater., 168, 208-219 (1989).

Ion-Bombardment Effects on Film Adhesion

R. A. Erck, G. R. Fenske, and A. Erdemir

To be presented at the 1989 Fall Mtg. of the Materials Research Society, Boston, MA, November 27-December 2, 1989.

Effect of Film Adhesion on Tribological Properties of IBAD-Coated Ceramics

R. A. Erck, A. Erdemir, and G. R. Fenske

Presented at 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-6, 1990, abstract in Program and Abstracts booklet, p. A-87.

Adhesion of Silver Films to Ion-Bombarded Alumina

R. A. Erck and G. R. Fenske

Proc. 1989 MRS Fall Mtg., Boston, MA, November 27-December 2, 1989, Materials Research Society, Pittsburgh, PA, 1990, pp. 85-90.

Measurements of Ion-Beam Dose with a Laser Sensor

R. A. Erck and R. Paitich (Terranova Scientific Inc.)

Submitted to Nucl. Instrum. & Meth. Phys. Res.

Effect of Film Adhesion on Tribological Properties of Silver-Coated Alumina

R. A. Erck, A. Erdemir, and G. R. Fenske

To be published in Proc. 17th Intl. Conf. on *Metallurgical Coatings* April 2-6, 1990, San Diego, CA.

Adhesion of Silver Films to Ion-Bombarded Zirconia

R. A. Erck and G. R. Fenske

To be presented at 1990 Joint *Tribology* Conf., Toronto, Canada, Oct. 7-10, 1990.

Microhardness of IAD-Silver Films

R. A. Erck

TRIB-ECUT-89/3 (July 1990), pp. 93-94.

Adhesion of IBAD Coatings

R. A. Erck and V. Mori

TRIB-ECUT-89/4 (October 1990), pp. 89-90.

IBAD Process Development

R. A. Erck and V. R. Mori

TRIB-ECUT-89/4 (October 1990), pp. 99-100.

Adhesion of IBAD Coatings

R. A. Erck

TRIB-ECUT-90/1 (February 1990), pp. 111-113.

Measuring Ion Beam Power with a Laser Sensor

R. A. Erck

Presented at 37th Ann. Symp. of the American Vacuum Society, Toronto, Canada, Oct. 8-12, 1990, abstract in Final Program, p. 127.

Adhesion of IBAD Coatings on Alumina and Zirconia

R. A. Erck

TRIB-ECUT 90/2 (June 1990), pp. 121-123.

Uses of Ion Bombardment in Thin-Film Deposition

R. A. Erck, G. R. Fenske, and A. Erdemir

To be presented at The Metallurgical Society Ann. Mtg., New Orleans, LA, Feb. 17-21, 1991.

Tribological Behavior of Ion-Plated TiN Coatings under Sliding and Rolling Contact

A. Erdemir and R. F. Hochman (Georgia Institute of Technology)

Proc. Conf. on *Ion Implantation and Plasma-Assisted Processes for Industrial Applications*, Atlanta, GA, May 23-25, 1988, ed. Robert F. Hochman, Hillary Solnick-Legg, and Keith O. Legg, ASM International, Metals Park, OH (1989), pp. 43-50.

Cross-Sectional Transmission Electron Microscopy of the Interfaces between Physical Vapor-Deposited TiN_x Coatings and Steel Substrates

A. Erdemir and C. C. Cheng

J. of Vac. Sci. Technol. A 7(3), 2486-2490 (May/June 1989). (Proc. Am. Vac. Soc. 35th Natl. Symp. and Topical Conf., Atlanta, GA, October 3-7, 1988.)

Nucleation and Growth Mechanisms in Ion-Plated TiN Films on Steel Substrates

A. Erdemir and C. C. Cheng

Surf. Coat. Technol. 41 285-293 (1990).

Effect of Sliding Velocity on the Wear Behavior of Polycrystalline Al₂O₃ and Silver-Coated Al₂O₃

A. Erdemir, G. R. Fenske, R. A. Erck, and D. Busch

INVITED TALK to be presented at 45th Ann. Mtg. of the Soc. of Tribologists and Lubrication Engineers, Denver, CO, May 7-10, 1990.

Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part II: Formation and Self-Lubricating Mechanisms of Boric Acid Films on Boron- and Boric-Oxide-Containing Surfaces

A. Erdemir, G. R. Fenske, R. A. Erck, F. A. Nichols, and D. Busch

INVITED TALK to be presented at 45th Ann. Mtg. of the Soc. of Tribologists and Lubrication Engineers, Denver, CO, May 7-10, 1990.

Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part I: Crystal Chemistry and Self-Lubricating Mechanism of Boric Acid

A. Erdemir

INVITED TALK to be presented at 45th Ann. Mtg. of the Soc. of Tribologists and Lubrication Engineers, Denver, CO, May 7-10, 1990.

Structure, Property and Performance Characteristics of HCD Ion-Plated TiN Coatings

A. Erdemir (Georgia Institute of Technology), W. B. Carter (Georgia Institute of Technology), and R. F. Hochman (Ga. Inst. of Tech.)

Proc. Fall Mtg. of AIME, 2nd Intl. Conf. on *Surface Modification Techniques*, Chicago, IL, September 26-28, 1988, ed. T. S. Sudarshan and D. G. Bhat, The Minerals, Metals & Materials Society, Warrendale, PA, 1989, pp. 261-278.

Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part II: Formation and Self-Lubricating Mechanisms of Boric Acid Films on Boron- and Boric-Oxide-Containing Surfaces

A. Erdemir, G. R. Fenske, R. A. Erck, F. A. Nichols, and D. Busch

To be published in Proc. 45th Ann. Mtg. of the Soc. of Tribologists and Lubrication Engineers, Denver, CO, May 7-10, 1990.

Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part I: Crystal Chemistry and Self-Lubricating Mechanism of Boric Acid

A. Erdemir

To be published in Proc. 45th Ann. Mtg. of the Soc. of Tribologists and Lubrication Engineers, Denver, CO, May 7-10, 1990.

Self-Lubricating Boric Acid Films for Tribological Applications

A. Erdemir, G. R. Fenske, F. A. Nichols, R. A. Erck, and D. E. Busch

Presented at the Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Tribological Properties of Thin Films on Ceramic Surfaces Prepared by Ion-Beam-Assisted Deposition

A. Erdemir, R. Erck, G. R. Fenske, C. C. Cheng, D. Busch, and F. A. Nichols

To be presented at the Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Ion-Assisted Deposition of High-Temperature Lubricious Surfaces

A. Erdemir, G. R. Fenske, R. A. Erck, and C. C. Cheng

Proc. 35th STLE/ASME Tribology Conf., Fort Lauderdale, FL, October 16-19, 1989, The Society of Tribologists and Lubrication Engineers, 1989, Preprint No. 89-AM-5C-1, pp. 1-8.

Solid Lubrication of Ceramic Surfaces by IAD-Silver Coatings for Heat Engine Applications

A. Erdemir, G. R. Fenske, F. A. Nichols, and R. A. Erck

Proc. 35th STLE/ASME Tribology Conf., Fort Lauderdale, FL, October 16-19, 1989, The Society of Tribologists and Lubrication Engineers, 1989, Preprint No. 89-TC-2E-1, pp. 1-8.

Self-Lubricating Boric Acid Films for Tribological Applications

A. Erdemir, G. R. Fenske, F. A. Nichols, R. A. Erck, and D. E. Busch

Proc. 1990 Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990, pp. 1797-1802.

Tribology of Surface-Engineered Ceramics

A. Erdemir, R. A. Erck, G. R. Fenske, and F. A. Nichols

INVITED TALK to be presented at 92nd Mtg. of the Am. Ceram. Soc., Dallas, TX, April 1990.

Ion-Beam-Assisted Deposition of Silver Films on Zirconia Ceramics for Improved Tribological Behavior

A. Erdemir, D. E. Busch, R. A. Erck, G. R. Fenske, and R. H. Lee

INVITED PAPER: Proc. Joint STLE-ASME *Tribology* Conf., Toronto, Canada, October 7-10, 1990, STLE Preprint No. 90-TC-1C-1, pp. 1-10.

A Study of the Formation and Self-Lubricating Mechanisms of Boric Acid Films on Boric Oxide Coatings

A. Erdemir, G. R. Fenske, and R. A. Erck

Presented at 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-6, 1990, abstract in Program and Abstracts booklet, p. A-31.

High-Temperature Tribological Characteristics of Silver and Gold Coatings on Ceramics Prepared by Ion-Beam-Assisted Deposition

A. Erdemir, R. A. Erck, G. R. Fenske, and F. A. Nichols

Presented at 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-6, 1990, abstract in Program and Abstracts booklet, p. A-46.

Structure and Tribological Characteristics of Silver Films on Ceramic Surfaces Prepared by Ion-Beam-Assisted Deposition

A. Erdemir, R. A. Erck, C. C. Cheng (Inland Steel Research Lab.) G. R. Fenske, and F. A. Nichols

Presented at 14th Intl. Conf. on *Surface Modification Techn.*, Nov. 6-9, 1990, Paris, France.

A Study of the Formation and Self-Lubrication Mechanisms of Boric Acid Films on Boric Oxide Coatings

A. Erdemir, G. R. Fenske, and R. A. Erck

To be published in Proc. 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-9, 1990.

Ion-Beam Processing of Advanced Ceramics for Improved Tribological Behavior

A. Erdemir, R. A. Erck, and G. R. Fenske

To be presented at *Cermatec '90* Mtg., Dearborn, MI, June 12-13, 1990.

IAD Silver Coatings on Ceramics

A. Erdemir, D. E. Busch, G. R. Fenske, and R. A. Erck

TRIB-ECUT-89/3 (July 1990), pp. 96-99.

Tribological Characterization of Si_3N_4 Ceramics

A. Erdemir and R. H. Lee

TRIB-ECUT-89/4 (October 1989), pp. 93-96.

Formation and Self-Lubrication Mechanisms of Boric Acid Films on Boron Coatings

A. Erdemir, D. Busch, and G. R. Fenske

TRIB-ECUT-89/4 (October 1989), pp. 97-99.

Tribological Characterization of Si_3N_4

A. Erdemir, R. A. Erck, and R. H. Lee

TRIB-ECUT-90/1 (February 1990), pp. 113-120.

IAD-Boric Oxide Coatings on Superalloys

A. Erdemir

TRIB-ECUT-89/3 (July 1989), p. 100.

Tribological Characterization of IBAD-Silver Coatings on Zirconia Ceramics

A. Erdemir, D. E. Busch, R. A. Erck, G. R. Fenske, and R. Lee

TRIB-ECUT 90/2 (June 1990), pp. 123-129.

Tribological Characterization of Boric Acid Films

A. Erdemir, D. E. Busch, G. R. Fenske, and R. A. Erck

TRIB-ECUT 90/2 (June 1990), pp. 129-133.

Effect of Postdeposition Annealing on Structure and Chemistry of the TiN Film/Steel Substrate Interfaces

A. Erdemir and C. C. Cheng (Inland Steel Co.)

To be presented at American Vacuum Society 37th Ann. Symp. and Topical Conf., Toronto, Canada, Oct. 7-10, 1990.

Cross-Sectional Transmission Electron Microscopy Study of Phase Transformations at TiN Film/Steel Substrate Interfaces

A. Erdemir and C. C. Cheng (Inland Steel Co.)

To be published in Proc. 3rd Conf. of Frontiers of *Electron Microscopy* in Materials Science, Oak Brook, IL, May 20-24, 1990.

Ion Beams "Nail" Thin Films

G. Fenske and R. A. Erck

INVITED PAPER: *logos* 8 (2), 9-14 (Spring 1990).

Nitride and Carbide Coatings for High Speed Steel Cutting Tools

G. R. Fenske

Tribol. Trans. 3(3), 339-345 (1989). (Proc. ASME-STLE Tribology Conf., Baltimore, MD, October 16-19, 1988.)

Ion Beam-Assisted Deposition of Adherent, Lubricious Coatings on Ceramics

G. R. Fenske, R. A. Erck, A. Erdemir, V. R. Mori, and F. A. Nichols

To be presented at the Japan Intl. *Tribology* Conf., Nagoya, Japan, October 29-November 1, 1990.

Engineered Tribological Surfaces

G. R. Fenske

TRIB-ECUT-89/3 (July 1990), pp. 89-141.

Ion-Beam-Assisted Deposition of Lubricious Compounds

G. R. Fenske

TRIB-ECUT-89/3 (July 1990), p. 93.

Ultra-Microhardness Measurements

G. R. Fenske and R. H. Lee

TRIB-ECUT-89/3 (July 1990), pp. 95-96.

IAD Process Development

G. R. Fenske

TRIB-ECUT-89/3 (July 1990), p. 100.

Engineered Tribological Surfaces

G. R. Fenske

TRIB-ECUT-89/4 (October 1990), pp. 85-139.

Ion-Beam-Assisted Deposition of Lubricious Compounds

G. R. Fenske

TRIB-ECUT-89/4 (October 1990), p. 89.

Ultra-Microhardness Measurements

G. R. Fenske and R. H. Lee

TRIB-ECUT-89/4 (October 1990), p. 92-93.

Engineered Tribological Interfaces

G. R. Fenske

TRIB-ECUT-90/1 (February 1990), pp. 107-137.

Ion-Beam Assisted Deposition of Lubricious Compounds

G. R. Fenske

TRIB-ECUT-90/1 (February 1990), pp. 111-113.

Engineered Tribological Interfaces

G. R. Fenske

TRIB-ECUT-90/2 (June 1990), pp. 117-119.

Ion-Beam-Assisted Deposition of Lubricious Compounds

G. R. Fenske

TRIB-ECUT 90/2 (June 1990), p 121.

Ion-Beam Mixing of Lubricous Layers On Metallic Alloys

G. R. Fenske and R. Hu

TRIB-ECUT 90/2 (June 1990), pp. 133-160.

Ion-Beam Mixing of Fe/B Layers for Triological Applications

G. R. Fenske, R. Hu, P. M. Baldo (MSD), R. A. Erck, A. Erdemir, R. H. Lee, D. E. Busch, F. A. Nichols, and L. E. Rehn (MSD)

To be presented at Joint STLE-ASME Tribology Conf., Toronto, Canada, Oct. 7-10, 1990.

Ion-Beam Mixing of Fe/B Layers for Tribological Applications

G. R. Fenske, R. Hu, P. M. Baldo (MSD), R. A. Erck, A. Erdemir, R. H. Lee, D. E. Busch, F. A. Nichols, and L. E. Rehn (MSD)

Society of Tribologists and Lubrication Engineers, presented at ASME/STLE Tribology Conference, Toronto, Ontario, Canada, Oct. 8-10, 1990, pp. 1-8.

Ion-Beam-Assisted Deposition of Adherent Lubricious Coatings on Ceramics

G. R. Fenske, R. A. Erck, A. Erdemir, V. R. Mori, and F. A. Nichols

To be presented at 17th Leeds-Lyon Symp. on *Tribology*, Leeds, England, Sept. 4-7, 1990.

Tribological Performance of Ion-Beam-Mixed Fe/B Multilayers on M-50 Steel

R. Hu, G. R. Fenske, L. H. Rehn, R. H. Lee, and R. A. Erck

Presented at 17th Intl. Conf. on *Metallurgical Coatings*, San Diego, CA, April 2-6, 1990, abstract in Program and Abstracts booklet, p. A-110.

Ion Beam Mixing of Lubricious Surfaces on Metallic Alloys

R. Hu and G. R. Fenske

TRIB-ECUT-89/3 (July 1990), pp. 101-116.

Ion-Beam Mixing of Lubricious Surfaces on Metallic Alloys

R. Hu and G. R. Fenske

TRIB-ECUT-89/4 (October 1990), pp. 100-102.

Ion-Beam Mixing and Tribology of Fe/B Multilayers

R. Hu, L. E. Rehn, G. R. Fenske, and P. M. Baldo

Presented at Symp. A, 1989 Fall Mtg. of Mater. Res. Soc., Boston, MA, November 27-December 2, 1989.

Ultramicrohardness of Thin Films

R. H. Lee

INVITED PAPER to be presented at *INTER/MICRO-90* Conf., Chicago, IL, August 21, 1990.

Tribological Technology Interchange

A. I. Michaels

TRIB-ECUT-89/3 (July 1990), p. 173.

Industrial Technology Interchange

A. I. Michaels

TRIB-ECUT-89/3 (July 1990), pp. 187-189.

Tribological Technology Interchange

A. I. Michaels

TRIB-ECUT-89/4 (October 1990), pp. 175-176.

The Modeling of Wear in Energy Conversion and Utilization Technologies

F. A. Nichols, A. I. Michaels, and L. A. Northcutt, Editors

Proc. International Workshop on *Wear Modeling*, Argonne National Laboratory, Argonne, IL, CONF-8806370 (June 1989).

Preface to the International Workshop on *Wear Modeling*

F. A. Nichols, A. I. Michaels, and D. G. Mello

Proc. Intl. Workshop on *Wear Modeling*, Argonne National Laboratory, Argonne, IL, June 16-17, 1988, pp. 1-2.

The Potential for Wear Modeling in Energy Conservation

F. A. Nichols and M. B. Peterson

Proc. Intl. Workshop on *Wear Modeling*, Argonne National Laboratory, Argonne, IL, June 16-17, 1988, pp. 5-24.

Tribology Project Research Report 89.1, Effect of Cylinder Distortions and Piston Ring Effects on Oil Consumption and Friction Losses in Automobile Engines

F. A. Nichols and A. I. Michaels, Editors

Prepared for the U.S. Department of Energy, ECUT Tribology Program.

Quarterly Progress Report, DOE-ECUT Tribology Program, April-June 1989

F. A. Nichols and A. I. Michaels

TRIB-ECUT-89/3 (July 1990).

Quarterly Progress Report, DOE-ECUT Tribology Program, July-September 1989

F. A. Nichols and A. I. Michaels

TRIB-ECUT-89/4 (October 1990), p. 78.

Quarterly Progress Report, DOE-ECUT Tribology Program, October-December 1989

F. A. Nichols and A. I. Michaels

TRIB-ECUT-90/1 (October 1990).

Quarterly Progress Report, DOE-ECUT Tribology Program, January-March 1990

F. A. Nichols and A. I. Michaels

TRIB-ECUT-90-2 (June 1990)

Irradiation Performance

Section Manager: L. A. Neimark

Principal Investigators: A. G. Hins, Y. Y. Liu, H.-C. Tsai

Support Staff: D. A. Donahue, J. E. Sanecki

Salaried Staff and Technicians: D. J. Evans, W. C. Kettman, F. Pausche, Jr.,

D. O. Pushis, F. E. Savole

Secretary: E. L. Hartig

Visiting Scientist: T. Mitsugi¹

The principal objective of the programs in this Section is to determine and assess the behavior of materials, principally fuels and claddings, in the core environment of nuclear reactors. This environment results in neutron damage and chemical, metallurgical, and mechanical processes that occur at high temperatures. The Section's present activities include fuel development for liquid-metal-cooled reactors and production reactors, and characterization of irradiated materials from light-water reactors. The Section operates the Alpha-Gamma Hot Cell Facility (AGHCF) and the Irradiated Materials Laboratory (IML), in which it conducts postirradiation examinations and investigations.

Fuel Development

Integral Fast Reactor

The Integral Fast Reactor (IFR) program is ANL's initiative for development of an inherently safe liquid-metal-cooled reactor (LMR) in combination with an integral fuel-reprocessing facility. The fuel cycle is based on U-Pu-Zr alloy fuel, a system explored at ANL in the 1960s. The Section's current activities include lead responsibilities for a prototype fuel rod irradiation test in the Fast Flux Test Facility (FFTF), a fuel design variables test, a cladding materials test and a series of transient overpower tests in EBR-II, investigation of irradiated and unirradiated fuel/cladding compatibility under off-normal conditions, and investigation of the effects of retained fission gas under off-normal conditions. The Section also performs some destructive examinations of EBR-II fuel rod experiments, conducts postirradiation fuel behavior tests for the ANL Fuels and Processes Division, and performs the post-test examination of fuel safety-related tests conducted by the Reactor Engineering Division (RE) in the TREAT reactor. Also, there is a joint effort with RE in investigating the behavior of whole irradiated fuel pins under simulated off-normal conditions in the AGHCF. The Section also assists in the fuel/cladding compatibility studies conducted by the Chemical Technology Division. It is anticipated that the IFR will account for a significant fraction of the Section's activities for the foreseeable future.

¹Japanese Power Reactor and Nuclear Fuel Development Corporation.

Advanced Oxide Transient Performance

The purpose of this LMR program is to investigate the transient overpower performance of advanced oxide fuel pin designs at slow ramp rates. This is a cooperative program between DOE and the Japanese Power Reactor and Nuclear Fuel Development Corporation. The program uses the unique capability of the EBR-II reactor for whole-core overpower events at slow ramp rates on the order of 0.01 to 10%/s. Phase II of the program, begun in September 1987, highlights advanced alloys for oxide fuels and is expected to be a seven-year effort. The Section's role is to conduct three transient overpower tests in EBR-II, conduct a series of whole-pin transient heating tests in the AGHCF, and perform all postirradiation examinations for the program's three experimenters in the AGHCF. The first of the overpower tests is scheduled for late 1991, and the transient heating tests are expected to begin toward the end of 1991.

New Heavy Water Production Reactor

The Irradiation Performance Section is involved in ANL's technology development efforts for DOE's new heavy-water-moderated reactor for the production of tritium. The Section is working with RE in the areas of transient fuel and target performance during severe accidents. Specifically, in-cell tests are conducted to investigate fuel expansion and fission-product release under simulated transient overpower conditions. The results are being used by modelers to predict how the fuel/target system will interact during such an event, and they are also being used to design the more prototypic in-reactor tests to be conducted later in the TREAT reactor. The initial scoping tests, in which a surrogate U-Al fuel was used, demonstrated the foaming potential of the fuel and the viability of our experimental approach. The in-cell tests will continue through 1992, while the RE in-reactor tests are expected to be evaluated between 1993 and 1995.

Characterization of Irradiated Materials

TMI-2 Lower Head Examination

The NRC, in conjunction with a consortium of foreign countries, has instituted a program to study possible effects on the properties of the TMI-2 lower vessel head. This study, which is centered in the Mechanics of Materials Section (MMS), is to determine the mechanical properties of samples, cut from the vessel, upon which a fraction of the molten core rested. Fifteen such samples were received from the reactor, decontaminated and inspected, and then passed on to the MMS for mechanical testing. An extensive crack in the stainless steel cladding of one sample was found to contain principally molten control-assembly constituents, thus adding to the scenario for core constituent relocation. The examination of fuel-bearing instrument tube nozzles in 1991 will conclude this TMI-2 program at ANL.

Assistance to Other Organizations

The capabilities of the AGHCF were utilized by a number of outside organizations, principally the Knolls Atomic Power Laboratory and the General Electric Co., to characterize irradiated or contaminated materials. Such efforts are expected to increase as the country's nuclear programs strive for a better understanding of radiation damage to the country's aging nuclear reactors. Also, the Irradiation Performance Section continues to maintain a role in the international effort to develop carbide fuel for LMRs, and some work in this area will be conducted in 1991.

Recent Work by the Irradiation Performance Section

Publications

Behavior of Mixed-Oxide Fuel Elements in a Tight Bundle under Duty-Cycle Conditions

T. Asaga (Power Reactor and Nuclear Fuel Development Corp., Japan), S. Shikakura (PNC), H. C. Tsai, and L. A. Neimark

Submitted to the Am. Nucl. Soc. 1990 Intl. *Fast Reactor Safety* Mtg., Snowbird, UT, August 12-16, 1990.

Behavior of Mixed-Oxide Fuel Elements in a Tight Bundle under Duty-Cycle Conditions

T. Asaga (Power Reactor and Nuclear Fuel Development Corp., Japan), S. Shikakura (PNC), H. C. Tsai, and L. A. Neimark

To be presented at 11th Intl. Conf. on *Structural Mechanics in Reactor Technology* (SMIRT), Tokyo, Japan, Aug. 18-23, 1991.

CERMET Fueled Reactors for Direct Nuclear Propulsion

L. W. Carlson (EP), S. K. Bhattacharyya (EP), K. D. Kuczen (EP), N. A. Hanan (EP), A. E. Knox (EP), and L. A. Neimark

Final Report for the Period February 1988 to November 1988, prepared for the Astronautics Laboratory (July 1989).

TMI-2 Vessel Investigation Project (VIP) Metallurgical Program

D. R. Diercks and L. A. Neimark

To be presented at the 18th *Water Reactor Safety Information* Mtg., Rockville, MD, October 22-24, 1990.

Metallurgical Reactions Involving Ag-In-Cd Control Rod Assemblies

Y. Y. Liu, L. A. Neimark, and W. D. Jackson

Nucl. Technol. 87, 95-103 (August 1989).

Whole-Pin Furnace System: An Experimental Facility for Studying Irradiated Fuel Pin Behavior under Potential Reactor Accident Conditions

Y. Y. Liu, H. C. Tsai, D. A. Donahue, D. O. Pushis, F. E. Savole, J. W. Holland (RAS), A. E. Wright (RAS), C. August (EP), J. L. Bailey (EP), and D. R. Patterson (EL)

Presented at the Am. Nucl. Soc. 1990 Intl. *Fast Reactor Safety* Mtg., Snowbird, UT, August 12-16, 1990.

Whole-Pin Furnace System: An Experimental Facility for Studying Irradiated Fuel Pin Behavior under Potential Reactor Accident Conditions

Y. Y. Liu, H. C. Tsai, D. A. Donahue, D. O. Pushis, F. E. Savole, J. W. Holland (RAS), A. E. Wright (RAS), C. August (EP), J. L. Bailey (EP), and D. R. Patterson (SSD-EL)

Proc. 1990 Intl. *Fast Reactor Safety* Mtg., Snowbird, UT, Aug. 12-16, 1990, Vol. 1, pp. 491-498.

Erosion-Corrosion of Materials at Elevated Temperature

K. Natesan and Y. Y. Liu

INVITED PAPER: Mater. Sci Eng. A121, 571-580 (1989). (Proc. 2nd Intl. Symp. on *High-Temperature Corrosion of Advanced Materials and Coatings*, Les Embiez, France, May 22-26, 1989).

The Microstructural and Microchemical Characterization of Samples from the TMI-2 Core

L. A. Neimark, R. V. Strain, J. E. Sanecki, and W. D. Jackson

INVITED PAPER: Proc. U.S. Nuclear Regulatory Commission 15th *Water Reactor Safety Information Mtg.*, Gaithersburg, MD, October 26-30, 1987, NUREG/CP-0091, Vol. 6 (February 1988), pp. 199-209; also Nucl. Eng. Des. 115, 315-321 (1989).

The Effect of Crystal Structure Stability on Swelling in Intermetallic Uranium Compounds

J. Rest, G. L. Hofman, and R. C. Birtcher

Proc. 14th Intl. Symp. on *Effects of Radiation on Materials*, Andover, MA, June 27-29, 1988, ed. H. Packan, R. E. Stoller, and A. S. Kumar, Vol. II, ASTM STP 1046, American Society for Testing and Materials, Philadelphia, PA, 1990, pp. 789-811.

Mechanistic Interpretation of an Observed Rate Dependence of Low-Temperature Swelling of Irradiated Uranium Silicide Dispersion Fuels

J. Rest and G. L. Hofman

To be published in Proc. 15th Symp. on *Effects of Radiation on Materials*, Nashville, TN, June 17-21, 1990.

Fuel Relocation Mechanism Based on Microstructures of Debris

R. V. Strain, L. A. Neimark, and J. E. Sanecki

Nucl. Technol. 87, 187-190 (August 1989).

Fuel/Cladding Compatibility in Irradiated Metallic Fuel Pins at Elevated Temperatures

H. Tsai

To be published in Proc. Am. Nucl. Soc. 1990 Intl. *Fast Reactor Safety Mtg.*, Snowbird, UT, August 12-16, 1990.

Performance of Fast Reactor Mixed-Oxide Fuel Pins during Extended Overpower Transients

H. Tsai, L. A. Neimark, T. Asaga (Power Reactor and Nuclear Fuel Development Corp., Japan), and S. Shikakura (PNC)

To be presented at 11th Intl. Conf. on *Structural Mechanics in Reactor Technology* (SMIRT), Tokyo, Japan, Aug. 18-23, 1991.

A Versatile Apparatus for Studying the Behavior of Irradiated Fuel

H. C. Tsai

Proc. 37th Conf. on *Remote Systems Technology*, 1989 Winter Mtg., San Francisco, CA, November 26-30, 1989, pp. 88-93.

Performance of Mixed-Oxide Fuel Elements during Extended Overpower Transients

H. C. Tsai and L. A. Neimark

To be presented at the Am. Nucl. Soc. 1990 Intl. *Fast Reactor Safety* Mtg.,
Snowbird, UT, August 12-16, 1990.

Fuel/Cladding Compatibility in Irradiated Metallic Fuel Pins at Elevated Temperatures

H. C. Tsai

Submitted to the Am. Nucl. Soc. 1990 Intl. *Fast Reactor Safety* Mtg., Snowbird, UT,
August 12-16, 1990.

Components Technology

Superconductivity Applications

Section Manager: J. R. Hull

Principal Investigators: Y. S. Cha, T. M. Mulcahy, K. L. Uherka

Secretary: J. A. Stephens

Visiting Scientists: M. C. Chyu,¹ F. C. Moon,² T. D. Rossing³

Students: S. A. Basinger,⁴ R. Korte,³ D. A. Yacobellis⁵

The special properties of superconducting materials allow many unique applications whose importance has increased significantly with the discovery several years ago of materials that superconduct at temperatures above the boiling point of nitrogen. The Superconductivity Applications Section conducts research and development on new applications of superconductivity and its support technologies. The work is both experimental and analytical.

Many of the Section's projects are funded by the Superconductivity Pilot Center at ANL; such projects are conducted with industrial collaborators, typically with each institution funding its own work but with staff from each institution working on the same project. Section members are thus frequently involved with industrial scientists and engineers in these collaborative programs. The Section collaborates closely with the MCT Ceramics Section in fabricating experimental superconducting devices, and with members of the ANL Energy Systems Division in developing magnetically levitated ground transport (maglev) systems.

Cryostat Current Leads

A cryostat current lead provides power from room-temperature sources to devices operating at liquid helium temperatures. Early analytical work showed that use of a high-temperature superconductor (HTS) in a lead has the potential to significantly reduce the helium boiloff in such devices. In collaboration with the Ceramics Section and the Westinghouse Research and Technology Center, a project was conducted to design, fabricate, and test a nominal 1-kA lead using HTSs. The superconducting portion of the lead, shown in the photo on the next page, was designed and fabricated at ANL. The complete lead was assembled and tested at Westinghouse. The HTS portion of the lead remained superconducting with currents as high as 2 kA, while helium boiloff from the lead

¹Texas Tech University.

²Cornell University.

³Northern Illinois University.

⁴University of Illinois at Urbana-Champaign.

⁵University of Illinois at Chicago.

*Photo of superconducting
portion of cryostat lead*

was approximately half that of the minimum obtained by the best theoretical lead consisting entirely of normal conductor. This was the first demonstration ever of such a low helium boiloff. Several Section projects are involved in further improving HTS current leads.

Magnetic Bearings

A collaborative project with the United Technologies Research Center explores the use of HTSs in magnetic bearing applications. In this project, the nature of the levitation force between permanent magnets and superconductors is studied by measuring the magnetic pressure, stiffness, and damping characteristics of different HTS materials. An apparatus has been developed to test the dynamic magnetic stiffness of the HTSs. Using this apparatus, we have discovered that the stiffness is highly amplitude-dependent. The utility of the apparatus is such that other researchers frequently send samples to our group for characterization.

Superconducting Magnetic Energy Storage

Superconducting magnetic energy storage (SMES) can efficiently store electrical energy for long periods of time. Members of the Section have worked on several collaborative projects that have investigated the use of HTSs in SMES. A collaborative project with CBI, Inc., identified several new problems associated with the boiling-nitrogen cooling of large structures. This project also investigated the feasibility of using a mixture of neon and nitrogen to obtain boiling heat transfer at temperatures below 64 K. A collaborative project with Combustion Engineering examined the feasibility of HTS-SMES on a small scale. This project resulted in an improved analysis technique to calculate the heat loss of mechanical support members that transmit the magnetic pressure of the cryogenic SMES to room-temperature bedrock. Subsequently, the Section became involved in a collaborative project with W. J. Schafer & Associates and General Atomics on HTS-SMES design.

Section staff are collaborating with the Ceramics Section in the design and fabrication of a 10-kJ energy storage coil. This coil will demonstrate the use of HTS in a mini-SMES operation.

Maglev Systems

The Section is collaborating with members of the Energy Systems Division in the development of maglev systems, as part of the U.S. program to evaluate this technology. One project uses a rotating-wheel test facility, shown in the second photograph, on which experimental models of maglev vehicles are levitated over guideways mounted on the wheel to test levitation properties and vehicle dynamics. A novel form of levitation has been invented by one of the Section staff, and this concept, as well as more traditional maglev concepts, are being evaluated on the wheel.

Another project is examining the effects of joints on vehicle ride quality in a continuous guideway. A number of joint configurations have been tested experimentally by studying the forces on a permanent magnet levitated above a rotating aluminum disk on which different cuts are made. This work has resulted in an innovative joint design that minimizes the effect of the joint on ride quality.

Test wheel used to examine maglev system properties and dynamics

Recent Work by the Superconductivity Applications Section

Publications

Editorial

J. R. Hull

Sol. Energy 45 (4) 183 (1990).

Effect of Guideway Discontinuities on Magnetic Levitation Force

T. D. Rossing (Northern Illinois University), R. Korte (NIU), and J. R. Hull

To be presented at 5th Joint MMM-Intermag Conf., Pittsburgh, PA, June 18-21, 1991.

Design and Testing of a High-Temperature Superconducting Current Lead

J. L. Wu (Westinghouse Science and Technology Center), J. T. Dederer (WSTC), P. W. Eckels (WSTC), S. K. Singh (WSTC), J. R. Hull, R. B. Poeppel, C. A. Youngdahl, J. P.

Singh, M. T. Lanagan, and U. Balachandran

To be presented at 1990 *Applied Superconductivity*, Snowmass Village, CO, Sept. 24-28, 1990, Proc. to be published in IEEE Trans. Magn.

Analytical Thermal-Hydraulics

Section Manager: W. T. Sha

Principal Investigators: M. Bottoni, T. H. Chien, H. M. Domanus,

R. C. Schmitt, J. G. Sun

Secretary: S. A. Moll

The main research disciplines of the Analytical Thermal-Hydraulics Section are heat transfer; single-phase and multiphase fluid flow; and mathematical, phenomenological, and numerical modeling. The Section's research activities are divided into three major areas: (1) code development, physical modeling, and numerical simulations for reactor applications; (2) generic casting modeling; and (3) fossil energy applications and modeling.

Code Development, Physical Modeling, and Numerical Simulations for Reactor Applications

Code Development

Since 1976, the Section has been engaged in developing three-dimensional, steady/transient, single-phase/multiphase computer codes for predicting temperature, velocity, pressure, and phasic concentration distributions in reactor component/multicomponent systems under normal and off-normal operating conditions. The developed codes fall into two series, COMMIX and BODYFIT (see Tables 1 and 2). The two series have a wide range of applications and are complementary to each other. The COMMIX series has been developed for global thermal-hydraulic analysis of large complex systems, whereas the BODYFIT series employing boundary-fitted coordinate transformation and has been developed for examination of small specific regions and analysis of detailed local thermal-hydraulic phenomena in such regions. Development of the BODYFIT code has been stopped due to funding limitations.

COMMIX

The codes in the COMMIX series allow global analyses of heat transfer and fluid flow phenomena within a single component (such as a rod bundle, reactor plenum, piping system, or heat exchanger) or in a multicomponent system, i.e., a combination of these components. A unique feature of the COMMIX code is its use of a new porous-media formulation in which volume porosity, directional surface porosity, distributed resistance, and distributed heat sources or sinks are employed to analyze continuum/quasicontinuum flow domains. The concept of directional surface porosity is new; it greatly facilitates modeling of velocity and temperature fields in anisotropic media and it generally improves

Table 1. COMMLX Series

COMMLX-1	All
COMMLX-1A	are
COMMLX-1B	Single-
COMMLX-1C	Phase
COMMLX-Condenser	Condenser Single-Phase/Multispecies (under development)
COMMLX-MF	Single Phase/Multiphase (under development)

Table 2. BODYFIT Series

BODYFIT-1FE	Single Phase
BODYFIT-2FE	Single Phase/Two Phase
BODYFIT-2PF	Single Phase/Two Phase

resolution and accuracy. The full three-dimensional, transient, conservation equations of mass, momentum, and energy are solved as a boundary-value problem in space and as an initial-value problem in time. The COMMLX codes have been developed and refined over several years, and a large number of computations for complex situations already have been performed to validate the general features and wide range of applications. The status of the following two COMMLX codes is described below.

COMMLX-1C

COMMLX-1C is the latest COMMLX series of single-phase codes and represents a significant improvement over the previous versions of single-phase COMMLX codes. Specifically, these improvements are (1) a new finite-volume formulation for the mass, momentum, and energy equations to extend the applications to subsonic compressible flows and to make the calculations more robust; (2) a flow-modulated skew-upwind discretization scheme to reduce numerical diffusion; (3) two new matrix solvers for the discretized equations to increase the flexibility and efficiency of numerical computation; and (4) a $k-\epsilon$ two-equation turbulence model that is more robust and better validated than those in previous COMMLX codes. Documentation of the COMMLX-1C code was completed in September 1990 and released through the Office of Nuclear Regulatory Research of the U.S. Nuclear Regulatory Commission.

Condenser Code (COMMIX-Condenser)

Condenser performance can significantly influence the overall performance of an entire power plant. The typical power plant condenser is a shell-and-tube heat exchanger. Steam enters the condenser from the turbine exhaust and mixes with leaked air flowing through the tube bundle. The steam is condensed to the liquid state by releasing the latent heat of vaporization. This latent heat is transferred to the cooling water through the condenser tubes. As the steam and air mixture moves toward the heat transfer surface, the noncondensable gases accumulate on the tube surfaces. These gases can significantly increase the thermal resistance between the steam and cooling water, thus reducing the steam condensation rate. To improve the heat transfer rate, the noncondensable gases must be reduced and removed.

Although the noncondensable gases have a significant effect on the performance of a condenser, performance also depends on tube material, tube wall thickness, local steam pressure, steam velocity, cooling water velocity, and effects of inundation and biofouling. To improve and optimize the design and performance of a power plant condenser, we are developing a new computer code based on the incomplete in-house version of the COMMIX-2A computer code. This is a three-dimensional, time-dependent, multi-component (multispecies) shell-and-tube-condenser computer code with the following features: shell- and tube-side heat transfer coupling; computing of both shell-side and tube-side velocity, temperature, and pressure distributions of steam and cooling water and air concentration distribution on shell side; and accounting for effects of inundation, vapor shear, and biofouling. This work is sponsored by the Taiwan Power Company, and the code development work will be completed by 1992.

Physical Modeling and Numerical Simulations

Natural Circulation

Natural circulation in the reactor coolant system (RCS) of a pressurized water reactor is defined as the phenomenon wherein buoyancy-driven coolant circulates between the core and upper plenum and between the reactor vessel and the steam generator. Natural circulation during a PWR accident transfers decay heat from the core to the structures in the upper plenum, hot legs, and steam generators. As a consequence, natural circulation has a significant impact on the course of the accident and its consequences. The NRC has identified natural circulation as an important process that can prevent direct heating of the containment and has indicated that natural circulation in the RCS is a major area of uncertainty on which near-term research effort should be focused.

In response to this new NRC research focus, we have placed a greater emphasis on modeling of natural circulation. During the past year, limited validations of the COMMIX-1C code have been performed and compared with the Westinghouse 1/7-scale natural circulation experimental data and the analytical results of a cavity problem. In the cavity problem, the flow is driven by the natural circulation that is set up because one wall of the

cavity is hotter than the opposite wall. Agreement between the calculated results and the experimental data is reasonably good. However, more assessment and validation of the COMMIX-1C code for natural circulation is very desirable.

Flow Stratification

Flow stratification is known to occur in various reactor components during normal and off-normal operating conditions in both PWRs and BWRs. A large temperature difference is normally associated with flow stratification. Thus, when flow stratification occurs in a reactor component, it will be subject to an additional thermal stress from the local temperature difference. A number of nuclear power plants have reported failure of reactor components due to flow stratification. Flow stratification not only can cause reactor shut-down due to an unisolable leak resulting from failure of a reactor component, but also has significant implications to reactor safety and can alter both the sequence and consequence of a reactor accident. Therefore, it is imperative to understand the causes of flow stratification; more important, we should be able to predict when and where flow stratification will occur and its magnitude of temperature difference associated with the flow stratification. Recently, the NRC Office for Analysis and Evaluation of Operational Data asked us to look into the problem and to develop an analytical capability in this area.

An analysis is being performed with the COMMIX-1C computer program for the surge line of the Comanche Peak reactor. The major objective of this analysis is to demonstrate that the COMMIX code can predict flow stratification. The numerical results obtained from the COMMIX code for the surge line of the Comanche Peak reactor have been compared with measurements provided by the Westinghouse Electric Corporation and the agreement is good. We expect to undertake an in-depth investigation of flow stratification.

Generic Casting Modeling

Fluid Flow and Heat Transfer Phenomena in the Casting Process

Casting is one of the most direct methods of producing industrial parts or components in desired shapes. Although the casting process has been in existence for thousands of years, it involves a host of complex phenomena that are still not thoroughly understood. The principal phenomena are fluid flow and heat transfer, because they control grain size and shape, porosity, and segregation of alloying elements in the final cast product. The flows in casting molds typically have free surfaces as well as moving solidification boundaries. Air and other gases may be trapped within the molten material, forming a two-component mixture. Nonuniform heat transfer, coupled with large temperature gradients and buoyancy forces, produces natural-convection currents in the molten metal. In certain circumstances, the flow may exhibit turbulence.

Casting Modeling is a new research and development program involving a consortium that comprises ANL, Caterpillar, and Teledyne Corporation and that started in March 1990.

The objective is to develop state-of-the-art software for simulating the mold-casting process; this is of immediate use to members of the casting industry. Expected benefits include superior castings produced with significantly reduced capital and operating costs. In this regard, each percentage-point reduction in the defect rate of the nation's casting industry would result in an annual energy savings of \$38 million. Furthermore, the program will benefit new product development, when first-run rejects are excessive and often cost-prohibitive. The importance of this program is further confirmed by industry's participation, which provides a 50% cost share for Phase I over a three-year period ending in 1993.

Casting Modeling: Filling of a wheel mold at different times.

(a) 0.05 s; (b) 0.15 s; (c) 0.35 s

The project draws upon the experience obtained while developing computer programs at ANL for the analysis of nuclear reactor systems, under the Analytical Thermal-Hydraulic Research Program. The new extensions will simulate the phenomena of mold filling and solidification. Transient free- and fixed-surface thermal hydraulics is a unique feature of this software, which is currently not available to industry. The interface for this model will be provided by existing software packages that are compatible with hardware currently in use or affordable by industry. Phase I of this project will produce a software package for distribution in the public domain by the American Foundrymen's Society. Subsequently, the project will continue without government participation to work on proprietary problems of industry.

In progress to date, selected features of three-dimensional, transient, thermal-hydraulic computer codes were ported from a mainframe system to a purchased SUN engineering workstation and made operational along with pre- and postprocessing software. Procedures were developed in the UNIX operating system to compile and modify the codes, to perform thermal hydraulic simulations, and to graphically display the results using POSTSCRIPT for hard copy and SUNCORE for screen display. The collection of data for casting parameters was accomplished through visits to consortium-member foundries and subsequent discussions. Development of the mold-fill model and the solidification model have begun. Some preliminary results from a simulation of the filling of a wheel mold are shown in the accompanying illustration.

A critical aspect of the project is to develop a user-friendly interface to be used in constructing the simulation and interpreting the results. A license has been obtained and the PATRAN software package has been installed on the project's engineering workstation. This represents the first use of this industry standard software package at ANL.

Fossil Energy Applications and Modeling

In the past year, we have been working on two new initiatives in the fossil energy area. One is the formulation of governing equations and constitutive relations of flotation processes for coal precleaning. The other is coordination of multiphase flow research.

Mathematical Modeling of Flotation Processes for Coal Cleaning

Mathematical modeling with a view toward optimizing the flotation process used in coal cleaning, whether conventional (or batched) froth flotation or column flotation, has been formulated to include mass and momentum balances. Previous mathematical modeling has been limited to mass balance based on a kinetic analogy, with a rate constant of collection that can be expressed in terms of probability or efficiency of collection. The present formulation includes the momentum equations in which velocities of phases are explicitly accounted for as dependent variables. It is applicable to both conventional froth flotation and column flotation.

A set of multiphase conservative equations for the flotation process has been developed and presented to demonstrate our approach toward computer modeling, taking into account primary interactions of phases. Transport properties associated with these

conservation equations are now expressed in terms of probability or efficiency of collection with the identification of generation rates, time constants for momentum transfer, diffusivities, and apparent viscosities. Terms involving interfacial chemistry of the particles and gas bubbles in a liquid suspension and other basic physical phenomena have been grouped into these transport properties. The need remains for accurate determination of the transport parameters with pertinent experimental data concomitant with the volume-averaged formulation of the equations of conservation for flotation processes. A report titled *Modeling and Optimization of Flotation Processes for Coal Precleaning* has been written and will be published soon.

Coordination of Multiphase Flow Research

Multiphase flow research is a cooperative research effort with universities. This research consists of two ongoing projects. One is *Investigations of Particulate Motion in Turbulent Flow by Optical and X-ray Image Technique*, with Professor Ronald Adrian of the University of Illinois at Urbana-Champaign; the other is *Interfacial Phenomena and Dynamics of Bubble Wakes in Gas-Liquid-Solid Flows*, with Professor Liang-Shih Fan of Ohio State University. Significant progress has been made on both projects.

Recent Work by the Analytical Thermal-Hydraulics Section

Publications

Practical Superconductor Development for Electrical Power Applications, Annual Report for FY 1988

U. Balachandran, I. D. Bloom (CMT), S. E. Dorris, J. T. Dusek, J. E. Emerson, K. C. Goretti, K. E. Gray, J. R. Hull, R. T. Kampwirth, M. T. Lanagan, H. J. Leu, V. A. Maroni, R. L. McDaniel, J. J. Picciolo, J. P. Singh, L. R. Turner, and C. A. Youngdahl
ANL-88-37 (February 1989).

Amplitude-Dependence of Magnetic Stiffness in Bulk High-Temperature Superconductors
S. A. Basinger, J. R. Hull, and T. M. Mulcahy
Submitted to Appl. Phys. Lett.

Numerical Simulation of Mixing in the Inlet Plenum of the Westinghouse 1/7-Scale Steam Generator Model
Y. S. Cha, H. M. Domanus, and W. T. Sha
ANL/ATHRP-40 (January 1990).

Validation and Assessment of the k - ϵ Two-Equation Turbulence Model in the COMMIX Code
Y. S. Cha, H. M. Domanus, and W. T. Sha
ANL/ATHRP-42 (February 1990).

Levitation Force and Magnetic Stiffness in Bulk High-Temperature Superconductors
P.-Z. Chang (Cornell U.), F. C. Moon (Cornell U.), J. R. Hull, and T. M. Mulcahy
J. Appl. Phys. 67(9), 4358-4360 (May 1, 1990).

Drag Force and Magnetic Stiffness in Bulk High-Temperature Superconductors
P.-Z. Chang (Cornell University), F. C. Moon (Cornell U.), and J. R. Hull
Submitted to Jpn. J. of Applied Physics

An Investigation of Error Introduced in Geometrical Approximations Used in the COMMIX Code for an Arbitrary Boundary Surface
T. H. Chien, H. M. Domanus, and W. T. Sha
ANL/ATHRP-41 (March 1990).

Validation of the COMMIX-1C Computer Code under Conditions of Natural Convection of Air in a Square Cavity by Comparison with the Benchmark Numerical Solution
T. H. Chien and W. T. Sha
ANL/ATHRP-43 (July 1990).

COMMIX-1C: A Three-Dimensional Transient Single-Phase Computer Program for Thermal-Hydraulic Analysis of Single- and Multicomponent Engineering Systems, Volume I: Equations and Numerics
H. M. Domanus, Y. S. Cha, T. H. Chien, R. C. Schmitt, and W. T. Sha
NUREG/CR-5649, ANL-90 (September 1990).

COMMLX-IC: A Three-Dimensional Transient Single-Phase Computer Program for Thermal-Hydraulic Analysis of Single- and Multicomponent Engineering Systems. Vol. II: User's Guide and Manual

H. M. Domanus, Y. S. Cha, T. H. Chien, R. c. Schmitt, and W. T. Sha
NUREG/CR-5649, ANL-90/33, Vol. II (1990).

Processing Thallium-Based Superconductors

K. C. Goretta, M. T. Lanagan, J. R. Hull, J. L. Routbort, D. L. Shi, N. Chen, and M. C. Hash (CMT)

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Kelvin-Helmholtz Instability and Cooling Limitations of a Vertical Molten Sheet Confined by Alternating Magnetic Fields

John R. Hull

Trans. ASME 111, 352-356 (May 1989).

Steady-State Analysis of the Rising Solar Pond

J. R. Hull and C. E. Nielsen (The Ohio State University)
Sol. Energy. 42(5), 365-377 (1989).

Ammonium Sulfate Solar Pond: Observations from Small-Scale Experiments

J. R. Hull, D. L. Bushnell (Northern Illinois University), D. G. Sempsrote (NIU), and A. Pena (University of Texas at El Paso)

Sol. Energy 43(1), 57-64 (1989); also to be published in Proc. Am. Sol. Energy Soc. Conf., Denver, CO, June 15-18, 1989.

Magnetohydrodynamic Stability in the Electromagnetic Levitation of Horizontal Molten-Metal Sheets

J. R. Hull, T. Wiencek, and D. M. Rote (ES)

Phys. Fluids A. 1(6), 1069-1076 (June 1989).

Stabilization of a Molten-Metal/Coolant-Gas Interface by Electromagnetic Fields

J. R. Hull and D. M. Rote (ES)

Phys. Fluids A. 2(3), 443-446 (March 1990)

Attractive Levitation for High-Speed Ground Transport with Large Guideway Clearance and Alternating-Gradient Stabilization

J. R. Hull

INVITED PAPER: Vector, Electromagnetics Newsletter 5(2), 4-6 (Summer 1989).

Maintenance of Brine Transparency in Salinity Gradient Solar Ponds

J. R. Hull

J. Solar Energy Engineering, Vol. 112, (1990), pp.65-69.

High-Temperature Superconducting Current Leads for Cryogenic Apparatus

J. R. Hull

Submitted to Cryogenics.

High-Temperature Superconductors for Space Power Transmission Lines

J. R. Hull and I. T. Myers (NASA Lewis Research Center)

Superconductivity Advances and Applications - 1989, ed. D. N. Palmer, The American Society of Mechanical Engineers, New York, 1990, Vol. 9, pp. 49-53. (Proc. ASME Winter Ann. Mtg, San Francisco, CA, December 10-15, 1989).

Contemporary Issues in Solar Pond Research

J. R. Hull

To be presented at the 2nd Intl. *Progress in Solar Ponds* Conf., Rome, Italy, March 25-31, 1990.

Contemporary Issues in Solar Pond Research

J. R. Hull

To be presented at the Am. Sol. Energ. Soc. Ann. Conf., Austin, TX, March 19-22, 1990.

Phenomenology of Forces Acting between Magnets and Superconductors

J. R. Hull, T. M. Mulcahy, L. Lynds (United Technologies Research Center), B. R.

Weinberger (UTRC), F. C. Moon (Cornell University), and P.-Z. Chang (Cornell U.)

Proc. 25th *Intersociety Energy Conversion Engineering* Conf., Reno, NV, Aug. 12-17, 1990, ed. Paul A. Nelson, William W. Schertz, and Russell H. Till, American Institute of Chemical Engineers, New York, 1990, Vol. 2, pp. 432-437.

Contemporary Issues in Solar Pond Research

J. R. Hull

To be published in Proc. Am. Sol. Energ. Soc. Ann. Conf., Austin, TX, March 19-22, 1990.

Characterization of Composite High-Temperature Superconductors for Magnetic Bearing Applications

J. R. Hull, T. M. Mulcahy, B. R. Weinberger (United Technologies Research Center), and L. Lynds (UTRC)

To be presented at 1990 *Applied Superconductivity* Conf., Aspen CO, Sept. 24-28, 1990.

Editorial

J. R. Hull

Submitted to Sol. Energy.

Phenomenology of Forces Acting between Magnets and Superconductors

J. R. Hull, T. M. Mulcahy, L. Lynds (United Technologies Research Center), B. R.

Weinberger (UTRC), F. C. Moon (Cornell University), and P.-Z. Chang (Cornell U.)

To be published in Proc. *Intersociety Energy Conversion Engineering* Conf., Reno, NV, August 12-17, 1990.

Heat Transfer Issues in the Fabrication and Operation of Ceramic Superconductors

J. R. Hull, T. M. Kuzay, and R. B. Poeppel

INVITED PAPER to be presented at American Society of Mechanical Engineers Winter Ann. Mtg., Dallas, TX, Nov. 25-30, 1990.

Materials Research Issues in Superconducting Levitation and Suspension as Applied to Magnetic Bearings

F. C. Moon (Cornell University) and J. R. Hull

Presented at the *Intersociety Energy Conversion Engineering Conf.*, Reno, NV, August 12-17, 1990.

Materials Research Issues in Superconducting Levitation and Suspension as Applied to Magnetic Bearings

F. C. Moon (Cornell University) and J. R. Hull

Proc. 25th *Intersociety Energy Conversion Engineering Conf.*, Reno, NV, Aug. 12-17, 1990, ed. Paul A. Nelson, William W. Schertz, and Russel H. Till, American Institute of Chemical Engineers, New York, 1990, Vol. 2, pp. 425-437.

Use of High-Temperature Superconductors in Superconducting Magnetic Energy Power Sources

D. N. Palmer (Combustion Engineering), J. R. Hull, T. M. Kuzay, and S. M. Schoenung (W. J. Schafer Associates, Inc.)

To be presented at 34th Intl. *Power Sources Symp.*, Cherry Hill, NJ, June 25-28, 1990.

Fabrication Advances for Improved Performance of Long Lengths of High-Temperature Superconducting Wire and Tape.

R. B. Poeppel, J. R. Hull, U. Balachandran, S. E. Dorris, J. T. Dusek, K. C. Goretta, M. T. Lanagan, J. J. Picciolo, and J. P. Singh

To be presented at 1990 Superconductivity Conf., Aspen, CO., Sept. 24-28, 1990.

Superconductivity: Opportunities for Mechanical Engineers

S. M. Schoenung (W. J. Schafer Associates, Inc.), M. I. Flik (University of California at Berkeley), and J. R. Hull

Submitted to *Mech. Eng.*

Status of Collaborative Research in the Solid Transport Area Between Midwest Universities and Argonne National Laboratory

W. T. Sha and R. J. Adrian (University of Illinois at Urbana-Champaign)

To be published in Proc. PETC Contractors Review Mtg. for *Solids Transport Program*, Pleasanton, CA, May 16-18, 1989.

Aeronautical Applications of High-Temperature Superconductors

G. E. Turney (Lewis Research Center), R. W. Luidens (Lewis Res. Ctr.), K. Uherka, and J. Hull

Prepared for Aircraft Design, Systems and Operations Conf., Seattle, WA, July 31-August 2, 1989, NASA Technical Memorandum 102311.

Recent Advances in Magnetic Heat Pump Technology

K. L. Uherka, J. R. Hull, and P. E. Scheihing (DOE)

Presented at ASME 1989 Winter Annual Mtg., San Francisco, CA, Dec. 10-15, 1989. Published in *Advances in Industrial Heat Pumps Technology-1989*.

Magnetic Bearings Using High-Temperature Superconductors: Some Practical Considerations

B. R. Weinberger (United Technologies), L. Lynds (UT), and J. R. Hull

Submitted to *Superconducting Science and Technology*

Design and Testing of a High-Temperature Superconducting Electrical Lead

J. L. Wu (Westinghouse Science and Technology Center), J. T. Dederer (WSTC), P. W. Eckels (WSTC), S. K. Singh (WSTC), J. R. Hull, R. Poeppel, C. Youngdahl, J. P. Singh, M. Lanagan, and U. Balachandran

To be presented at 1990 *Applied Superconductivity* Conf., Aspen, CO, Sept. 24-28, 1990.

Patents

Electromagnetic Augmentation for Casting of Thin Metal Sheets

John R. Hull

U.S. Patent No. 4,846,255 awarded July 11, 1989.

Thermal and Mechanical Sciences

Section Manager: M. W. Wambsganss

Principal Investigators: S. S. Chen, U. S. Choi, J. A. Jendrzejczyk, K. E. Kasza

Support Staff/Visiting Scientists: Y. Cai, D. M. France,¹ N. T. Obot¹

Technicians: D. M. Engel, R. K. Smith

Secretary: J. A. Stephens

Students: T. Tran²

Staff backgrounds and program activities in the Thermal and Mechanical Sciences Section relate to many diverse areas involving structural dynamics, thermal hydraulics, heat transfer, fluid flow, and vibrations. Staff expertise and experience is primarily in experimentation and testing, but also extends to modeling. A particular strength of the Section is its test facilities. These include the Flow-Induced Vibration Test Facility (an 8,000-gpm water flow loop), the Flow and Heat Transfer Test Facility (a computer-controlled, thermal-hydraulic, transient, nonisothermal, 2,200-gpm water loop), a low-velocity water channel, a slurry test facility, an adiabatic two-phase flow apparatus, and a 500-gpm water loop. The Section performs fundamental research, component development, and performance testing, and provides consultation. Current activities include research in the areas of flow-induced vibration, multiphase flow and heat transfer in compact heat exchanger geometries, ice slurries for district cooling, advanced energy-transmission fluids, and vehicle dynamics and guideways for high-speed trains using magnetic levitation. In addition, vibration studies are performed in support of the Advanced Photon Source (APS) project, preparations are being made for thermal-hydraulic studies in support of the new production reactors, and consulting is being carried out for the NRC/NRR and the Taiwan Power Company (Taipower).

Flow-Induced Vibrations

Section staff have been involved in a continuing program in flow-induced vibration for more than 20 years. Several projects have recently been completed:

- A program jointly sponsored by DOE and Northeast Utilities Service Company developed a method for predicting the response of loosely supported tubes experiencing fluidelastic instability. The method is based on the unsteady flow theory for fluidelastic instability of tube arrays and uses force coefficients available in the literature.

¹Special Term Appointee.

²Purdue University.

- A three-year program sponsored by the DOE Office of Basic Energy Sciences (BES) investigated fluidelastic instabilities associated with leakage flow between closely spaced components. Several model problems were formulated and studied to gain insights into the underlying mechanisms.
- In cooperation with Heat Transfer Research, Inc. (HTRI), seven new case histories of field experience with heat exchanger tube vibration were added to the DOE/ANL/HTRI Tube Vibration Data Bank. The number of cases in the data bank now totals 82. The data bank represents a source of information that designers and researchers can reference when evaluating heat exchanger designs from the standpoint of flow-induced vibration or in the evaluation of prediction methods.

A new three-year DOE/BES-sponsored program, to be performed in collaboration with Cornell University, was recently initiated with the objective to develop and apply methods for identifying and characterizing nonlinear and chaotic vibrations in fluidelastic systems. In particular, the study is intended to improve the physical understanding and provide mathematical modeling of the nonlinear dynamic interactions associated with a tube caused to oscillate between motion-limiting stops by the self-excited fluidelastic instability experienced by a tube row in a sufficiently high-velocity crossflow. Experiments will be performed with a row of tubes, because this is the only tube array for which sufficient information is available to perform an analysis.

A new initiative to be funded by Taipower is in the final stages of approval. The subject is flow-induced vibration in heat exchangers and steam generators. The proposed work covers a three-year period and includes the development of analytical methods and computer programs, measurements and calculation of flow velocities and fluid forces, and tests and prediction of tube wear.

Multiphase Flow and Heat Transfer

Fundamental studies of multiphase flow and heat transfer in flow channels representative of compact heat exchangers of the plate-fin type are being performed under sponsorship of the DOE Office of Energy Conservation, Advanced Industrial Concepts Division. Plate-fin heat exchangers have certain unique characteristics that suggest their application in vapor-compression refrigeration cycles using nonazeotropic refrigerant mixtures as the working fluid. Because flow maldistribution is an inherent problem in all multichannel flow arrangements, and because the problem is exacerbated when the flow is two-phase, single-channel studies are being emphasized initially. In particular, small rectangular channels, with hydraulic diameters on the order of 1 to 6 mm, are being studied.

Adiabatic experiments with air/water mixtures have been performed in horizontal, rectangular channels of different sizes and orientations. Results have led to data bases of flow pattern information and pressure-drop measurements. Using these data bases, we have generated two-phase flow pattern maps and a pressure gradient correlation developed to include mass velocity effects. Future experiments include air/R-113 mixtures with the

objective to evaluate fluid-property effects such as surface tension. Fabrication of a heat transfer test apparatus is in progress. The ultimate objective of the heat transfer tests is to measure heat transfer coefficients associated with the phase-change heat transfer of non-azeotropic refrigerant mixtures.

*Two-phase flow pattern map (top) and photographs of horizontal two-phase flow (bottom).
 G = total mass flux.*

Thermal Hydraulics in Support of NPR Development

Two new production reactors (NPRs), a heavy water reactor (HWR) and a modular high-temperature gas reactor (MHTGR), are being designed to replace the aging reactors at DOE's Savannah River Plant. A DOE-sponsored program was conducted at ANL to design an in-vessel thermal-hydraulic test of the NPR-HWR. The objectives of the test would be to explore the sensitivity to disruption by thermal buoyancy of reactor vessel flow and thermal distributions during transitions to natural circulation. A test model was designed and a series of model-scaling calculations were performed; the calculations established physical dimensions and operating ranges for the scaled water model. We believe that the model tests are necessary to ensure transition to natural circulation and adequate flow in all the fuel tubes. However, at present, the HWR designers (EBASCO) plan to perform only isothermal steady-state tests. Consequently, actual performance of the planned testing is uncertain.

Ice Slurries for District Cooling

Ice-water slurries have the potential for realizing significant energy savings and cost reduction in district cooling systems. Taking advantage of the latent heat associated with the ice crystals permits the pumping of a higher-energy-density fluid. As a result, the piping, which represents a major cost in a district cooling system, can be much smaller. There are also potential savings associated with the heat exchangers, as they too can be smaller and can be made to operate more efficiently. DOE has funded earlier investigations of ice slurries at ANL and elsewhere. To focus these efforts, ANL has proposed a four-year district cooling field testing program to the DOE Utility Systems Division, for joint sponsorship with Northern States Power (NSP) and the Electric Power Research Institute (EPRI); the initial test will involve providing of cooling to the NSP utility service center. The three proposed sponsors have agreed to the program and it is expected that the program will be initiated in 1991. The ANL role is to provide project management for DOE, in addition to performing development testing and participating in data analysis and interpretation.

The district cooling field tests with ice slurries are planned to, among other things, showcase the technology. However, it is acknowledged that the system for field testing will not be optimally designed. Ultimately, application of this technology and the design of optimized systems will require validated design correlations for both heat transfer and pressure drop. While some work on pressure drop has been performed, the results are mixed. Heat transfer, which is important in during slurry transport and in heat exchangers, has yet to be addressed in detail in the engineering literature. ANL has proposed, for DOE's consideration, a program of fundamental studies of ice slurries to be performed as a joint effort with the University of Illinois at Chicago. The objective of this research is to develop design correlations for heat transfer and pressure drop with ice-slurry flows. The correlations would be functions of such parameters as ice crystal size and ice volume fraction. It is expected that the program will be initiated in 1991. This will allow the use of preliminary results in the design of the field tests, as well as provide basic information and insights that will be of use in subsequent evaluation of the field test results.

Advanced Energy Transmission Fluids

District heating and cooling systems are characterized by long distribution pipes that convey a pumped energy transmission fluid between the source and sink heat exchangers of the system. In a closed-loop DHC system, the addition of a friction-reducing additive (FRA) to the working fluid would allow reduced pumping power and/or smaller diameter pipes. ANL has been engaged in a continuing program to study friction-reducing additives; its pilot-scale DHC system simulator is the only large-scale facility available for testing such additives.

Promising FRAs for DHC applications have been identified on the basis of tests in laboratory-scale loops with small pipes. It is known that the additives are less effective in large pipes than in small ones. Current efforts, under a program sponsored by the DOE Utility Systems Division, involve scale-up experiments with the objective to evaluate the effectiveness of select additives in a large (6-in. diameter) pipe system. The experiments involve the measurement of both pressure drop and heat transfer for a range of additive concentrations and operating temperatures corresponding to DHC system conditions. The reference case of pure water and the first phase tests with Ethoquad R/13-50 have been completed. A chiller will be installed in the facility to extend the temperature range down to that required for district cooling applications (40°F). A second additive (Separan) will then be evaluated. Also, technical discussions have been held with researchers from Ohio State University regarding the evaluation by ANL of new additives under development in their OSU laboratory.

7-GeV Advanced Photon Source

Section staff have been involved in an ongoing program of vibration studies in support of the design and development of the 7-GeV APS. The APS is a user facility for synchrotron radiation research. Its successful operation requires a stable positron closed orbit. The fact that vibration of the storage ring quadrupole magnets can lead to distortion of the positron closed orbit and to potentially unacceptable beam emittance growth provides the motivation for the studies. The vibration criteria are very stringent (on the order of 0.1 μm for frequencies greater than ~ 15 Hz).

Among other things, Section staff have been engaged in a vibration measurement program that has included measurements of ground motion at the APS site and measurements of vibration levels at select ANL facilities to gain insights into the amplitudes that might be expected. Current efforts are focused on the magnet support assemblies, which consist essentially of a girder mounted on three jackscrew supports. Testing, including modal testing, and finite-element analyses were performed with the objectives of understanding and characterizing the dynamic behavior (natural frequencies, modes, and damping) of the assemblies, evaluating different jackscrew support configurations, and determining nominal response to floor motion and coolant flow through a header and return piping attached to the girder. The test setup with the storage ring magnets simulated by concrete blocks is shown in the photograph. The chart shows a typical bending mode of the girder, as determined by modal testing. Conclusions and recommendations from the studies are communicated to the appropriate APS project technical groups.

Maglev Studies

Section staff are contributing to the maglev program at ANL with an emphasis on the guideways for high-speed trains. The technical approach involves establishment of baseline information on state-of-the-art technologies relative to guideways, vehicles, magnet field, and flow field; collation of engineering data in these areas; identification of research needs; and recommendation of technical approaches (analyses and/or tests) required to obtain the necessary data and to develop computer codes and design guides.

*Test setup for APS magnet support assembly;
concrete blocks simulate the
storage ring magnets*

Consulting

Consulting efforts are valuable in that they allow Section staff to become aware, at an early date, of real-life problems and concerns faced by utilities and industry. Additionally, consulting provides an opportunity to apply the expertise developed in the course of conducting fundamental and applied research.

The Section has provided consultation to the NRC Office of Nuclear Reactor Regulation on an "as-needed" basis since 1982. The primary focus of the consulting has been on issues relating to flow-induced vibration of steam generator tubes.

The Section also provides consultation to Taipower in flow-induced vibrations and related areas. Completed efforts included the presentation of short courses at the Taipower site, evaluation of flow-induced vibration of component cooling water heat exchangers, and evaluation of fluid/structure interaction of fuel assemblies in fuel storage racks.

Recent Work by the Thermal and Mechanical Sciences Section

Publications

Amplitude-Dependence of Magnetic Stiffness in Bulk High-Temperature Superconductors

S. A. Basinger, J. R. Hull, and T. M. Mulcahy

Submitted to Appl. Phys. Lett.

Performance of a Multi-Grid Three-Dimensional MHD Generator Calculation Procedure

J. X. Bouillard (ES), J. L. Krazinski, S. P. Vanka, and G. F. Berry (ES)

Proc. 27th Symp. on *Engineering Aspects of Magnetohydrodynamics*, Reno, NV, June 27-29, 1989, ed. J. Martin Bauer, The American Society of Mechanical Engineers, New York, (1990), pp. 5.2-1-5.2-11.

User's Manual for MGMHD: A Multigrid Three-Dimensional Computer Code for the Analysis of Magnetohydrodynamic Generators and Diffusers

J. X. Bouillard (ES), J. L. Krazinski, S. P. Vanka, and G. F. Berry (ES)

ANL/MHD-89/1 (1990).

Levitation Force and Magnetic Stiffness in Bulk High-Temperature Superconductors

P.-Z. Chang (Cornell University), F. C. Moon (Cornell U.), J. R. Hull, and T. M. Mulcahy

J. Appl. Phys. 67(9), 4358-4360 (May 1, 1990).

A Review of Two-Phase Flow-Induced Vibration

S. S. Chen

Proc. 6th Intl. Conf. on *Pressure Vessel Technology* (ICPVT-6), Beijing, China, September 1988, Paper No. AMRC-17, 1988, PVT-Vol. 1, pp. 172-190.

Fluidelastic Instabilities in Tube Bundles Exposed to Nonuniform Crossflow

S. S. Chen and S. Chandra (Northeast Utilities Service Co.)

To be presented at the ASME Pressure Vessel and Piping Division Conf., Nashville, TN, June 17-21, 1990.

Fluidelastic Instabilities in Tube Bundles Exposed to Nonuniform Crossflow

S. S. Chen and S. Chandra (Northeast Utilities Service Company)

ANL-89/13 (June 1989).

Flow-Induced Vibration

S. S. Chen

ANL/MCT-89/4 (November 1989).

Fluidelastic Instabilities in Tube Bundles Exposed to Nonuniform Crossflow

S. S. Chen and S. Chandra (Northeast Utilities Service Company)

To be published in Proc. ASME Pressure Vessel and Piping Division Conf., Nashville, TN, June 17-21, 1990.

Dynamic Tube/Support Interaction in Heat Exchangers

S. S. Chen

To be presented 5th Intl. Conf. on *Flow Induced Vibrations*, Brighton, England, May 21-23, 1991.

Unsteady Fluid Forces and Fluidelastic Vibration of a Group of Circular Cylinders

Chen, S. S.

INVITED PAPER to be presented at ASME Winter Annual Mtg., Forum on *Unsteady Flow*, Dallas, TX, Nov. 25-30, 1990.

Flow-Induced Vibration of an Array of Cylinders

S. S. Chen

INVITED PAPER to be published in *Shock and Vibration Digest*.

Dynamic Tube/support Interaction in Heat Exchanger Tubes

S. S. Chen

To be published in Proc. 5th Intl. Conf. on Induced Vibrations, Brighton, England, May 21-23, 1991.

Flow-Induced Vibration - 1990

S. S. Chen

ANL/MCT-90/2 (September 1990).

Flow-Induced Vibration of an Array of Cylinders, Part II

S. S. Chen

INVITED PAPER to be published in *Shock and Vibration Digest*.

Shellside Waterflow-Induced Tube Vibration in Heat Exchanger Configurations with Tube Pitch-to-Diameter Ratio of 1.42

H. Halle, J. M. Chenoweth (Heat Transfer Research, Inc.), and M. W. Wambsganss

J. Pressure Vessel Technol. 111, 441-443 (November 1989). (Proc. Intl. Symp. on *Flow-induced Vibration and Noise*, Chicago, IL, November 27-December 2, 1988.)

Phenomenology of Forces Acting between Magnets and Superconductors

J. R. Hull, T. M. Mulcahy, L. Lynds (United Technologies Research Center), B. R.

Weinberger (UTRC), F. C. Moon (Cornell University), and P.-Z. Chang (Cornell U.)

Proc. 25th *Intersociety Energy Conversion Engineering Conf.*, Reno, NV, Aug. 12-17, 1990, ed. Paul A. Nelson, William W. Schertz, and Russell H. Till, American Institute of Chemical Engineers, New York, 1990, Vol. 2, pp. 432-437.

Characterization of Composite High-Temperature Superconductors for Magnetic Bearing Applications

J. R. Hull, T. M. Mulcahy, B. R. Weinberger (United Technologies Research Center), and L. Lynds (UTRC)

To be presented at 1990 *Applied Superconductivity Conf.*, Aspen CO, Sept. 24-28, 1990.

Phenomenology of Forces Acting between Magnets and Superconductors

J. R. Hull, T. M. Mulcahy, L. Lynds (United Technologies Research Center), B. R. Weinberger (UTRC), F. C. Moon (Cornell University), and P.-Z. Chang (Cornell U.)

To be published in *Proc. Intersociety Energy Conversion Engineering Conf.*, Reno, NV, August 12-17, 1990.

SHAM: High-Level Seismic Tests of Piping at the HDR

C. A. Kot, M. G. Srinivasan, B. J. Hsieh, L. Malcher (Kernforschungszentrum Karlsruhe, FRG), D. Schrammel (K.K., FRG), H. Steinhilber (Fraunhofer Institut für Betriebsfestigkeit, FRG), and J. F. Costello (U.S. Nuclear Regulatory Commission) *Nucl. Eng. Des.* 118, 305-318 (1990). (Proc. 16th *Water Reactor Safety Information Mtg.*, Gaithersburg, MD, October 24-27, 1988.)

High-Level Seismic Tests of Piping at the HDR

C. A. Kot, M. G. Srinivasan, B. J. Hsieh, and J. F. Costello (U.S. Nuclear Regulatory Commission)

Transactions 10th Intl. Conf. on Structural Mechanics in Reactor Technology, Anaheim, CA, August 14-18, 1989, American Association of Structural Mechanics in Reactor Technology, Los Angeles, CA, 1990, Vol. S, pp. 87-92.

One-Dimensional Leakage-Flow Vibration Instabilities

T. M. Mulcahy

Proc. 1988 Intl. Symp. on Flow Induced Vibration and Noise, Chicago, IL, Nov. 28-Dec. 2, 1988, The American Society of Mechanical Engineers, NY, 1989, Vol. 4, pp. 93-110.

Flow Enhancement of Annulus Damping

T. M. Mulcahy

Submitted to *J. Sound Vib.*

Use of High-Temperature Superconductors in Superconducting Magnetic Energy Power Sources

D. N. Palmer (Combustion Engineering, Inc.) and J. R. Hull

To be presented at the 34th Intl. *Power Sources Symp.*, Cherry Hill, NJ, June 25-28, 1990.

Fouling in Jet Fuels: A New Approach

W. M. Roquemore (WRDC/Aero Propulsion and Power Laboratory), J. A. Pearce (WRDC/Aero), W. E. Harrison III (WRDC/Aero), J. L. Krazinski, and S. P. Vanka

Proc. Symp. on The Structure of Future Jet Fuels II, Miami Beach, FL, September 10-15, 1989, American Chemical Society, Washington, DC, 1989, pp. 841-849.

Three-Dimensional Thermal-Hydraulic Analysis of a Liquid Metal Reactor Design with the COMMIX Computer Code

Y. W. Shin

Presented at 10th Conf. on *Structural Mechanics in Reactor Technology*, Anaheim, CA, August 14-18, 1989.

A Method for Suppression of Pressure Pulses in Fluid-Filled Piping: Theoretical Analysis

Y. W. Shin and A. H. Wiedermann (IIT Research Institute)

Proc. 1989 ASME PVP Conf., Honolulu, HI, July 22-26, 1989, ed. Y. W. Shin and F. J. Moody, The American Society of Mechanical Engineers, New York, 1989, PVP-Vol. 156, pp. 35-41.

Proceedings of 1989 ASME Pressure Vessel and Piping Conf., Honolulu, HI, July 22-26, 1989, PVP-Vol. 156, *Transient Thermal Hydraulics in Vessel and Piping Systems*

Y. W. Shin and F. J. Moody, Editors

The American Society of Mechanical Engineers, New York, 1989.

A Method for Pressure-Pulse Suppression in Fluid-Filled Piping

Y. W. Shin, E. F. Bieleck (EP), A. H. Wiedermann (IIT Research Institute), and C. E. Ockert (DOE)

Transient Thermal Hydraulics and Resulting Loads on Vessel and Piping Systems - 1990, Proc. 1990 Pressure Vessel and Piping Division Conf., Nashville, TN, June 17-21, 1990, ed. F. J. Moody, Y. W. Shin, and J. Colton, PVP, Vol. 190, The American Society of Mechanical Engineers, New York, (1990), pp. 9-16.

SWAAM Code Development, Verification, and Application to Steam Generator Design

Y. W. Shin and R. A. Valentin

INVITED PAPER: To be published in Proc. IAEA Specialists Mtg. on Generator Failure and Failure Propagation Experience, Aix-en-Provence, France, Sept. 26-Oct. 3, 1990.

Analytical Simulation of Seismic Testing of VKL Piping System at the HDR Test Facility

M. G. Srinivasan, C. A. Kot, and B. J. Hsieh

To be published in Proc. ASME 1990 *Pressure Vessels and Piping Conf.*, Nashville, TN, June 17-21, 1990.

An Efficient Computational Tool for Ramjet Combustor Research

S. P. Vanka, J. L. Krazinski, and A. S. Nejad (AFWAL/POPT, Wright Patterson Air Force Base)

Jet Propulsion Power 5(4), 431-437 (August 1989).

Analytical Studies of Three-Dimensional Combustion Processes

S. P. Vanka

AFWAL-TR-88-2140 (May 1989).

Two-Phase Flow Patterns and Transitions in a Small, Horizontal, Rectangular Channel

M. W. Wambsganss, J. A. Jendrzejczyk, and D. M. France (University of Illinois at Chicago)

Submitted to Intl. J. Multiphase Flow.

Two-Phase Flow Patterns and Frictional Pressure Gradients in a Small, Horizontal, Rectangular Channel

M. W. Wambsganss, J. A. Jendrzejczyk, D. M. France (University of Illinois at Chicago), and N. T. Obot (Clarkson University)

ANL-90/19 (1990).

Flow-Induced Vibration of Component Cooling Water Heat Exchangers

Y. S. Yeh (Taiwan Power Company) and S. S. Chen

Presented at the ASME *Pressure Vessel and Piping* Division Conf., Nashville, TN, June 17-21, 1990.

Flow-Induced Vibration of Component Cooling Water Heat Exchangers

Y. S. Yeh (Taiwan Power Company) and S. S. Chen

Flow-Induced Vibration - 1990, Proc. ASME *Pressure Vessel and Piping* Division Conf., Nashville, TN, June 17-21, 1990.

Dynamic Plastic Deformation of a Tube Loaded over a Time-Dependent Region

C. K. Youngdahl

Intl. J. Impact Eng. 9(1), 71-88 (1990).

Approximate Solutions for Dynamic Plastic Deformation of a Tube

C. K. Youngdahl

Transactions 10th Intl. Conf. on *Structural Mechanics in Reactor Technology*, Anaheim, CA, August 14-18, 1989, American Association of Structural Mechanics in Reactor Technology, Los Angeles, CA, 1990, Vol. J, pp. 103-108.

Modal Solutions for the Dynamic Plastic Deformation of a Beam

C. K. Youngdahl

INVITED PAPER submitted to J. Nucl. Eng. Des.

A Modal Approximation Method for Strain-Hardening Beams

Carl K. Youngdahl

Submitted to Int. J. Impact Eng.

Instrumentation and Nondestructive Evaluation

Section Manager: A. C. Raptis

Principal Investigators: S. L. Dieckman, W. A. Ellingson, N. Gopalsami,

D. S. Kupperman, K. J. Reimann, R. A. Roberts, S. H. Sheen,

Support Staff: J. Ackerman,¹ J. P. Bobis,¹ W. E. Brewer, G. A. Forster, K. Gopalan,

E. R. Koehl, W. P. Lawrence, T. Pillai,¹ K. Gopalan,¹ M. Vannier,¹ P. Rizo,

T. Luethi, T. Hentea, B. Chung

Technicians: R. N. Lanham

Secretary: N. M. Heeg

Students: R. Popper, M. J. Szuster, J. Vaitekunas, C. Lee, M. Beckman,

A. Bric, H. C. Liao

The Instrumentation and NDE Section conducts research and development in a broad range of energy-related technologies. Major areas of responsibilities are the development of instruments or NDE techniques for fossil energy, conservation, and nuclear technologies, as well as for arms control and verification treaties. In addition, the Section performs considerable work in conjunction with private industry. The projects described below give a clear indication of the breadth of the Section's work.

Arms Control

Millimeter-Wave Detection from Space of Chemical Weapon Plants (N. Gopalsami and A. C. Raptis)

This is a new program funded by DOE Office of Arms Control in the area of chemical weapons compliance (CWC) monitoring. Remote monitoring of chemical plants that can be converted to produce chemical warfare agents or their precursors is an important verification scenario in the effective implementation of CWC treaties. Millimeter-wave techniques (in the frequency range of 30 to 300 GHz) are investigated in this program for space-based or other remote detection of CW plants. The advantage of millimeter waves over visual or infrared optics is that they can penetrate through the atmosphere (in cloudy, snowy, or rainy weather, and day or night) with less attenuation. More important, the rotational and hyperfine transition (emission) frequencies of gaseous molecules are, for the most part, in the millimeter-wave spectrum and can be used to monitor CW plant effluents.

¹Special Term Appointee.

Ultrasonic Intrinsic Tag Evaluation (S. H. Sheen and W. P. Lawrence)

This program will develop an ultrasonic imaging system to study image variations of various composite materials. One objective of the program, which is funded by the DOE Office of Arms Control, is to determine whether a subsurface ultrasonic image can be used as a unique surface signature of the scanned material, thus allowing the image to be used as an intrinsic tag for the material. The program will also evaluate the performance of a portable ultrasonic imaging system developed by Battelle Pacific Northwest Laboratory. The vulnerability of the system and the spoofability of the subsurface tag will be evaluated. Work in this program is classified.

Assessment of Tamperproof Ceramic Seals (D. S. Kupperman, S. H. Sheen, and A. C. Raptis)

The DOE Office of Arms Control is funding efforts at ANL to develop new concepts in tags and seals for application to treaty inspection protocols. These devices could be used for production-facility shutdown, munitions storage facilities and demilitarization facilities for both nuclear and chemical weapons. A principal objective of this work is to provide a seal to verify that weapons have not been diverted during movement from storage to the destruction site. The seal must be designed to reveal tampering (break and repair) or replacement by a counterfeit.

A simple and rapidly authenticated tamperproof ceramic seal has been under development at ANL in FY 1990. This seal would resist state-of-the-art tampering, operate under severe conditions, and establish identity and integrity with one interrogation. The seal would be used, for example, on containers of various sizes and on valves or perimeter gates to establish whether tampering or entry has occurred. The feasibility of assembling a ceramic tamperproof seal with seeded defects has been established, and a laboratory system for rapid ultrasonic scanning of ceramic components has been assembled. Seeded zirconia samples and two seals have been fabricated.

Samples have been ultrasonically scanned, and the uniqueness of the ultrasonic fingerprint due to the seeded defects has been demonstrated. Commercially available image processing software has been used to correlate ultrasonic amplitude images and establish criteria for identification. Shrink fitting the connecting and binding parts has been demonstrated as feasible and essentially irreversible. Tests have demonstrated that ultrasonic waves can be coupled to the seal with commercially available ultrasonic gel pads.

While fabrication and authentication problems have been addressed, the potential difficulties associated with field implementation, however, have not been thoroughly studied. Thus, future efforts will be directed toward a conceptual design for a field-implementable scanner, self-checking procedures, calibration methods, and protocol for verification.

Fossil Energy

Ultrasonic Flow Imaging System (S. H. Sheen and W. P. Lawrence)

The goal of this program, which is funded by the DOE Fossil Energy AR&TD Program, is to develop an ultrasonic flow imaging instrument for mixed-phase flow measurements. Applied to a coal slurry flow, the imaging system will produce real-time flow images from which particle velocity profile, concentration, and size distribution will be determined. The instrument will consist of two arrays of transducers clamped to the outside pipe wall. The transducers will be sequentially pulsed to generate ultrasonic waves that propagate through the slurry. The attenuated and scattered ultrasonic signals will be detected by the transducers on the same plane. An image-reconstruction algorithm will be developed to produce real-time images for both attenuated and scattered signals. A correlation method will also be developed to obtain particle velocity profile. Along with instrument development, theoretical modeling of wave propagation in solid suspensions will also be investigated. The model will solve the scattering matrix for multiple particle scatterings.

Ultrasonic Nondestructive Evaluation (S. H. Sheen)

Ultrasonic NDE methods will be developed for evaluation of structural ceramic composites used in fossil energy processes. The focus of this Fossil Energy program is to establish a sensitive ultrasonic imaging technique to examine the porosity and whisker concentration in whisker-reinforced ceramic composites such as SiN/SiN and SiC/SiN through transmission and subsurface imaging methods. Transducers of frequencies greater than 10 MHz will be used. Normal and inclined incident ultrasonic beams will be tested for their sensitivity to structure defects. Measured whisker concentrations will be correlated with the mechanical strength of the composites; thus, the effect of the whiskers in the structural ceramic composites will be determined.

Fuel Cells (W. A. Ellingson)

The development of an all-ceramic fuel-cell is being jointly undertaken by ANL and the AiResearch Casting Division of Allied-Signal Aerospace Corporation. Funding is from DOE Fossil Energy. Fabrication of the all-ceramic fuel cell requires high reliability of each of the relatively thin (0.0100–0.0150 in.) layers. Of concern is uniformity of both density and thickness of each layer during processing, as well as detection of any cracks after complete fuel cell assembly. The hot-rolled calendaring operation used to manufacture the critical thin-layer tape has several variations that make detection after this operation almost mandatory. Several NDE methods are being studied for application to this problem.

Ceramic Composites (W. A. Ellingson, N. Gopalsami, and S. L. Dieckman)

Initiation of a fracture in a structural ceramic can often be traced to a flaw that was inadvertently introduced during processing and part-forming. Whisker-based or

continuous-fiber-based ceramic-ceramic composite materials show increased tolerance to small flaws. In a cooperative effort with the Ceramics Section, samples of Si_3N_4 -whisker-reinforced Si_3N_4 composites are being produced by both cold pressing and hot pressing in attempts to correlate flaw populations with fracture behavior. Detection of these flaws, such as whisker clumps and whisker alignment, can lead to predictive strength capability.

In cooperation with Oak Ridge National Laboratory, also funded by Fossil Energy, continuous-fiber SiC/SiC composites are being produced by a new process called chemical vapor infiltration (CVI). SiC cloth layups of 30, 60, 90 or 45, 90 are often used. Axial and radial density variations are of concern because low density means high void content and thus poor mechanical properties.

Because the primary "flaw type" (characteristic) of interest, in either of the above two examples of ceramic-ceramic composites, is variation in density, the primary instrumentation system under development for this is 3-D microtomography using X-rays. A 3-D X-ray tomographic imaging system has been designed and developed. The X-rays originate in a microfocus source that allows high magnification with minimum distortion. The detector is an image intensifier/CLD camera system. Data acquisition and control is handled by an IBM-PC and image reconstruction is performed in an ANL mainframe computer (a VAX 8700). The 3-D data display appears on the scientific visualization workstation, which is a Titan-Avdant supercomputer.

We have demonstrated this year that variations in whisker content from 0 to 35 vol.% can be tracked by using X-ray CT data. Because strength of these composites seems to be maximum at about 12-14 vol.%, detection of off-optimum whisker concentrations seems possible and thus in the green state, a first indication of strength variation seems to be detectable. We have further demonstrated this year that image data obtained by the X-ray CT system, when coupled to image processing, can be used to assess nonuniformity of whisker alignment. By taking approximately 700- μm -thick X-ray CT section images and then using 2-D Fourier transform image analysis, we showed that continuous-fiber orientations varied $\pm 5^\circ$ from the nominal values.

Conservation

Monolithic Ceramics (W. A. Ellingson, N. Gopalsami, and S. L. Dieckman)

Part 1

Near-term advanced heat engine components will likely be made of advanced monolithic structural ceramics. Because these materials are very susceptible to fracture by flaws, the detection of flaws and high reliability of ceramic production is imperative. In a joint activity with the Norton Advanced Ceramic Company, funded by the DOE Assistant Secretary for Conservation and Renewable Energy, we are playing an integral role in helping to improve Si_3N_4 ceramic processing reliability. We are actively engaged in three areas: (1) X-ray computed tomography for mapping density distributions in both slip-cast and

injection-molded specimens, (2) nuclear magnetic resonance imaging to map organic binder distributions and porosity distributions, and (3) nuclear magnetic spectroscopy for characterizing colloidal suspensions used in slip-casting and in powder preparation for injection molding.

We have demonstrated to Norton that radial density distributions in the 1-cm-diameter gage section have shown axial density variations throughout the tensile specimens. The radial density variations, in fact, demonstrated to Norton how a change in mold design had affected density distribution. Nuclear magnetic resonance (NMR) spectroscopy has been shown to be capable of detecting distributions of surfactants, deflocculants, and sintering aid that heretofore could not be measured.

Part 2

In another joint research activity with industry, this time with Garrett Ceramic Components of Allied-Signal Aerospace Corporation, we are developing NMR imaging relative to the sensitivity to distribution of organic binder distribution used in Si_3N_4 injection molding. By using a reasonably simple organic/powder loading test matrix, we developed both techniques and calibrations to provide an excellent idea of the potential sensitivity of NMR imaging to map the spatial distribution of organic material throughout the volume of a part. Results suggested that organic binder loadings can be mapped to within 0.5 wt.% at levels of 10–15 wt.%. This project is continuing, with the focus now on SiC-whisker-reinforced slip-cast Si_3N_4 . This is again a two-year effort. As part of this new program, correlations between NMR image data and X-ray CT image data will be studied to assess detection sensitivity to whisker clumps, density variations, etc.

Part 3

In cooperation with the Garrett Auxiliary Power Division of Allied-Signal Aerospace Corporation, we are assessing the potential of digital image processing to enhance the detection capabilities of ordinary X-ray films. A set of Si_3N_4 specimens was produced with known flaw populations of various types and sizes. We are digitizing these films by various methods, concentrating on full-field CCD cameras with back-lighted films. Once digitized, the data are then manipulated in the computer by various image processing methods, e.g., low-pass, high-pass filtering, 3 x 3 or 5 x 5 Laplacian filters, etc. At present, no analytical method seems available to systematically select the sequence of image processing steps to best enhance the features of interest.

Thick Thermal Barrier Coatings (W. A. Ellingson)

The development of high-efficiency diesel engines that can burn low-grade fuels necessitates the use of some type of ceramic coating on components exposed to the combustion zone. Plasma-sprayed ZrO_2 coatings are being developed by Caterpillar, Inc. In a project to be funded by the State of Illinois, NDE methods are to be developed to detect coating adhesion. Initial work will focus on time-resolved-infrared radiometry. This project is cofunded by the State of Illinois and Caterpillar Research.

NMR Spectroscopy and Imaging of Advanced Ceramics and Ceramic Composites (S. L. Dieckman and N. Gopalsami)

The objective of this work is to develop and evaluate advanced NDE methods based on NMR technology for characterization of the chemical and physical properties of advanced ceramic materials and components. Working in conjunction with the Norton Advanced Ceramics Company and Garrett Ceramic Components, we will evaluate the utility and impact of these techniques on processing technology. Technical highlights of recent work include the demonstration of chemical sensitivity via correlation of NMR imaging results with those obtained through destructive measurements; development of high-resolution 3-D imaging techniques for solid materials; application of 3-D imaging techniques to determine organic additive distribution in green-state Si_3N_4 tensile specimens; and demonstration of the complementary nature of NMR and X-rays for characterization of Si_3N_4 -whisker-reinforced Si_3N_4 matrix composites. Additionally, the development of NMR spectroscopic techniques for characterization of both the bulk and the surface of ceramic materials is being initiated. These techniques will be applied to the study of composite whisker/matrix and fiber/matrix interface chemistry. This work is supported by the DOE Fossil AR&TD program, by DOE Conservation, and by subcontract from Norton Advanced Ceramics through funding from DOE Conservation.

Assessment of Nondestructive Evaluation for Sodium Heat Engine Development (D. S. Kupperman, S. H. Sheen, S. Gopalsami, S. Dieckman, and A. C. Raptis)

The Sodium Heat Engine (S.H.E) is a self-contained device that converts heat directly to DC power. The S.H.E. is an ongoing development stemming from a 1968 patent of Ford Motor Co. With the principal scientific issues related to S.H.E. operation explored and an understanding of the operation reached, the emphasis is now shifting to solving to problems of reliability, operation, and durability. As a result of mechanical failures that terminated the operation of the test devices, the Section is addressing the issue of beta"-alumina solid electrolyte (BASE) durability. Effective and economic NDE methods and protocols are being sought to provide rapid evaluations of components during process development and prior to use.

Through-transmission optical scanning by means of an intense neon light inserted in the S.H.E BASE tubes has been used to rapidly scan the outer surface and near-surface region of the tubes. The translucent nature of the BASE tubes makes this technique viable. Computer interfacing is used to enhance defect indications, allowing flaws as small as 25 μm to be imaged. Defects detected optically can be missed by traditional X-ray methods used to inspect these tubes. X-ray tomography, on the other hand, does appear to be useful for detecting variations in density.

X-ray diffraction technology, used to measure surface residual stresses, has been applied to determine if high residual stresses are present in the BASE tubes. Preliminary indications are that, unexpectedly, tensile stresses are generated on the surface of the tubes as a result of the fabrication procedure. Neutron diffraction will also be used to obtain an estimate of the bulk residual stresses. The residual stresses could contribute to the limited lifetime of the BASE tubes.

An ultrasonic microscope has been modified to allow high-resolution scans of the BASE tubes to be made. This technology could be very useful because it can be used on-line, providing the economical and rapid mapping of defects and density variations.

Work for Others

Acid Rain Effects on Marble and Limestone (K. J. Reimann)

The study of effects of acid rain and weathering on marble and limestone is continuing. Field-exposed samples at several instrumented test sites in the eastern United States were analyzed for compositional changes by chemical means, material losses by gravimetry, and laser-moiré interferometry and tri-stimulus color measurements for discoloration. Chemical results for exposure periods of up to five years indicate an increase of sulfate concentration on the groundward surface proportional to the H^+ concentration and exposure period. Sulfate formation is orders of magnitude greater than formation of nitrate, chlorine, and fluorine on the groundward surface of exposed stones. Skyward surfaces exhibit no appreciable changes in these concentrations due to regular rinsing by rain. Material losses of exposed samples show a linear relationship with exposure time and amount of rain. Discoloration measured on exposed marble samples shows a yellowing on both the skyward and groundward surfaces. Exposed limestone shows a slight darkening of the skyward surfaces relative to that of the groundward surface, which is very pronounced. The yellowing of marble and darkening of limestone shows a linear relationship to the exposure period. Studies to correlate the different phenomena are confirming.

NMR Imaging of Polymeric Materials (S. L. Dieckman and N. Gopalasami)

This is a new project funded by the Dow Chemical Company. The goal is to develop advanced-solids NMR imaging techniques for measurement of chemical and physical properties of polymers and polymeric blends. Experimentation will focus on the development of specialized techniques necessary to obtain images with high spatial resolution and chemical sensitivity. These techniques will facilitate the nondestructive measurement of chemical properties such as extent of polymerization, molecular mobility, and solvent diffusion, as well as of physical properties such as internal flaws and domain sizes, in a variety of naturally occurring and synthetic polymeric materials.

Application of Neutron Diffraction to Determination of Strain in Engineering Materials (D. S. Kupperman and R. Popper)

In an interdisciplinary program involving the Intense Pulsed Neutron Source (IPNS) Division, the Instrumentation and NDE, Ceramics (J. P. Singh), and Mechanics of Materials (S. Majumdar) Sections, neutron diffraction has been applied to the study of residual stresses and strains in advanced engineering materials. This technology has direct application to problems in a variety of industries. Programs involving, for example, General Electric (high-temperature engines) and Westinghouse (ceramic cross-flow filter) are

already in place, while others involving the Electric Power Research Institute, DuPont, Dow Corning, and Allied-Signal are in the planning stages.

The primary effort has been in advanced composites. Motivation for this work is that fabrication-induced residual stresses play an important role in the lifetime of components made from these materials. The mechanical properties, such as strength and toughness, of advanced ceramic and metal-matrix composites can be greatly influenced by fabrication-induced residual stresses. Stresses are created when the two different materials used to form the composite are fired and cooled. Very large residual stresses (up to 2 MPa) can result. It is important in the optimization of mechanical properties to know the stress levels and how to modify them. Central to the problem is the ability to measure changes in the lattice spacing when the material is elastically strained. If the strain is in the elastic region and we know the elastic moduli of the material, we can determine the stress inside the material or the average stress of a constituent of a composite. Neutron diffraction can provide a bulk measurement of the lattice spacing of the constituents of a composite through the use of Bragg's Law. If both macrostresses (e.g., from welding or surface finish) and microstresses (those on the scale of the microstructure) are present, neutron diffraction averages out the macrostresses, thus making the microstresses directly accessible. This is a significant advantage over X-ray diffraction, which measures only near-surface stresses (including macrostresses).

Recently, the IPNS and the associated General Purpose Powder Diffractometer (GPPD) at ANL were used to measure the residual strains in various ceramic- and metal-matrix composites. These measurements were used to calculate stresses for comparison with predictions of analytical models to further enhance confidence in the measured elastic strain and calculated residual stresses.

Ceramic-ceramic composites with silicon carbide whiskers randomly embedded in an alumina matrix have been evaluated. Tests conducted at the IPNS showed that as temperature rises and falls, strain relaxes and intensifies. These observations also indicate that, during the temperature drop from 1700°C to about 1400°C, the material is relaxing by creep and is not building up residual stresses. It is apparent from experimental and analytical results that as the volume of the silicon carbide whiskers increases, the matrix strain (alumina) increases and the whisker strain (SiC) decreases (becomes less negative). It is desirable to incorporate enough whiskers to toughen the material, but not so much as to cause the matrix to crack. Neutron diffraction measurements can provide guidance for development of these composites.

IPNS measurements made in titanium matrix/silicon carbide fiber composites, as part of an ongoing joint program with General Electric, showed designers that the strains in the fibers are large (on the order of 1 GPa). The experimental results were in excellent agreement with analytical models developed by General Electric and validated their model assumptions. Reduction of the magnitude of the strains may mitigate the fatigue damage problem when this material is introduced into advanced engines.

Another example involves new high-temperature ceramic superconductors. It may be possible to improve the toughness of this monolithic material by adding silver to the ceramic to form a superconducting composite, but the combination of a metal and a ceramic is likely to cause the buildup of residual stresses during fabrication. The silver

contracts more than the ceramic matrix and could pull away from the ceramic material; thus breaking electrical continuity. The ceramic should be bonded so well to the silver that when it cools, it will pull the silver into tension. If the silver is in tension, compressive stresses should exist in the matrix, a situation that is desirable because when the matrix is in compression, the probability that cracks will propagate in it is minimized. Compressive stresses tend to squeeze a crack at its tip, preventing or at least minimizing its continued growth. Increasing compressive strain has been observed in the superconducting oxide $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, which forms the matrix (and also decreases tensile strain in the silver), as the volume concentration of the silver increases to 20%. This is a clear indication of good bonding of the oxide to the silver. The compressive strain relaxes at higher silver concentration, probably because the oxide is undergoing plastic deformation due to creep. Neutron diffraction is probably the only technique that could be used to demonstrate this effect.

Neutron diffraction provides a unique set of new tools for NDE and characterization of materials, particularly in the area of internal strains in complex structures. While these techniques are not adaptable to a manufacturing environment, they are very valuable for obtaining absolute measurements for validating and calibrating other methods that are easier to use.

Acoustic Leak Detection and Location for District Heating and Cooling Systems (D. S. Kupperman, W. Lawrence and R. Lanham)

An acoustic leak detection system developed and tested at ANL was applied to steam leak problems in the Consolidated Edison of New York (ConEd) district heating and cooling system. The leak location system incorporates sensitive, commercially available probes and advanced signal processing involving cross-correlation analysis to locate leaks. As part of a demonstration for ConEd, an underground leak was successfully located with acoustic sensors placed on pipes below manholes at two locations in the vicinity of the leak. Although this test helped minimize the extent of excavation needed to repair this particular leak, it also revealed problems with the current method of acoustic leak detection and location. A new program now being planned would lead to the development of an in-stream acoustic sensor that should greatly improve leak location capability. This program will be a joint effort involving ANL, ConEd, and the American Society of Heating, Refrigeration and Air Conditioning Engineers.

While problems associated with fabrication and authentication have been addressed, the potential difficulties associated with field implementation, however, have not been thoroughly studied. Thus, future efforts will be directed toward a conceptual design for a field implementable scanner, self-checking procedures, calibration methods, and protocol for verification.

**ANL/BIR Technology Exchange on Solid State NMR Imaging
(S. L. Dieckman and N. Gopalsami)**

This is a new project funded by the DOE/ANL Technology Transfer Center. It combines the expertise of both MCT and Bio-Imaging Research, Inc., in designing radio-frequency (RF) coils and associated electronics for NMR imaging of materials. The objective is to develop an advanced solid state NMR imaging probe with application to materials research and evaluation. Specifically, the advanced RF components, in concert with existing ANL solid state NMR imaging capability, will promote the use of this technology in areas that include ceramic technology, polymeric technology, and biomedical engineering.

Recent Work by the Instrumentation and NDE Section

Publications

NMR Spectroscopy and Imaging of Macerals in Argonne Premium Coals

R. E. Botto (CHM), C. Y. Choi (CHM), S. L. Dieckman, N. Gopalsami, A. R. Thompson (CHM), and C. J. Tsiao (CHM)

To be presented at 4th Australian Coal Conf., Brisbane, Australia, December 3-5, 1990.

Design of a Solid State NMR Imaging Accessory

S. L. Dieckman, N. Gopalsami, W. A. Ellingson, and R. E. Botto (CHM)

To be presented at 31st *Experimental Nuclear Magnetic Resonance Spectroscopy* Conf., Pacific Grove, CA, April 1-5, 1990.

RF Tuning with PACMAN (Phase Adjustment with Cartesian Mapping for NMR)

S. L. Dieckman, N. Gopalsami, and R. E. Botto (CHM)

TAMU NMR Newsletter 379, 27-30 (April 1990).

Three Dimensional Nuclear Magnetic Resonance and X-ray Computed Tomographic Imaging of Solid Materials

S. L. Dieckman, P. Rizo, N. Gopalsami, and R. E. Botto (CHM)

To be published in *J. Mater. Res. Soc.*

Nuclear Magnetic Resonance Imaging for Detecting Binder/Plasticizers in Green-State Structural Ceramics

W. A. Ellingson, J. L. Ackerman (Massachusetts General Hospital/Harvard Medical School), S. Gronemeyer (Siemens Medical Systems), and L. Garrido (Mass. Gen. Hosp./Harvard Med. Sch.)

Ceramic Transactions, ed. James D. Cawley and Charles E. Semler (Proc. *Silicon Carbide* 1987 Symp., Columbus, OH, August 2-5, 1987), The American Ceramic Society, Inc., Westerville, OH, 1989, Vol. 2, pp. 187-198.

Applications of Dual-Energy X-Ray Computed Tomography to Structural Ceramics

W. A. Ellingson and M. W. Vannier (Mallinckrodt Institute of Radiology/Washington University)

INVITED PAPER: Proc. 37th Ann. Denver Conf. on *Advances in X-Ray Analysis*, Steamboat Springs, CO, August 1-5, 1988, ed. C. S. Barrett, J. V. Gilfrich, R. Jenkins, T. C. Huang, and P. K. Predecki, Plenum Press, NY, 1989, pp. 629-640.

Development of Nondestructive Evaluation Methods for Structural Ceramics

W. A. Ellingson, R. A. Roberts, N. Gopalsami, S. L. Dieckman, J. P. Singh, and J. J. Vaitekunas

Presented at 3rd Ann. *Fossil Energy Materials Program* Contractors' Conf., Oak Ridge, TN, August 8-10, 1989; abstract in Program and Abstracts booklet, p. 47.

An Initial Comparison of X-Ray and NMR Computed Tomography for Detection of Organic Binder Distribution

W. A. Ellingson, P. S. Wong, S. L. Dieckman, J. P. Pollinger (Garrett Ceramic Components Division, Allied-Signal Aerospace Company), H. Yeh (Garrett/Allied-Signal), and M. W. Vannier (Mallinckrodt Institute of Radiology/Washington University) *Ceram. Eng. Sci. Proc.* 10(7-8), 1022-1031 (1989). (Proc. 13th Ann. Conf. on *Composites and Advanced Ceramics*, Cocoa Beach, FL, January 15-18, 1989.)

Nuclear Magnetic Resonance Imaging

W. A. Ellingson, P. S. Wong, S. L. Dieckman, and J. P. Pollinger (Garrett Ceramic Components Division, Allied-Signal Aerospace Company) *Ceramic Technology for Advanced Heat Engines Program: Semiannual Progress Report for the Period October 1, 1988, through March 31, 1989*, ORNL/TM11239 (August 1989), pp. 508-520.

Computed Tomography

W. A. Ellingson, H. P. Engel, M. W. Vannier (Mallinckrodt Institute of Radiology/Washington University), and H. C. Yeh (Garrett Ceramic Components Division, Allied-Signal Aerospace Co.) *Ceramic Technology for Advanced Heat Engines Program: Semiannual Progress Report for the Period October 1, 1988, through March 31, 1989*, ORNL/TM-11239 (August 1989), pp. 498-507.

Characterization of Ceramics by NMR and X-Ray CT

W. A. Ellingson, P. E. Engel (EG&G of Florida), T. I. Hentea (Purdue University-Calumet), K. Gopalan (Purdue U.-Calumet), P. S. Wong, S. L. Dieckman, and N. Gopalsami
To be presented at *Industrial Computerized Tomography Topical Conf.*, Seattle, WA, July 25-27, 1989.

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, R. A. Roberts, J. P. Singh, C. Y. Chu, N. Gopalsami, S. L. Dieckman, T. Hentea (Purdue University-Calumet), and J. J. Vaitekunas *Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending March 31, 1989*, ORNL/FMP-89/1 (July 1989), pp. 11-33.

Magnetic Resonance Imaging: A New Characterization Technique for Advanced Ceramics

W. E. Ellingson, P. S. Wong, S. L. Dieckman, J. L. Ackerman (Massachusetts General Hospital/Harvard Medical School), and L. Garrido (Mass. Gen. Hospital/Harvard Med. School) *Ceram. Bul.* 68(6), 1180-1186 (June 1989).

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, C. Y. Chu, N. Gopalsami, S. L. Dieckman, T. Hentea (Purdue University-Calumet), K. Gopalan, J. J. Vaitekunas

Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending September 30, 1989, ORNL/FMP-89/2, (January 1990) pp. 11-35.

X-Ray Computed Tomographic Imaging

W. A. Ellingson, T. Hentea (Purdue University-Calumet), K. Gopalan (Purdue U.-Calumet), H. Yeh (Garrett Ceramic Components Division of Allied-Signal Aerospace Corp.), and J. P. Pollinger (Garrett/Allied-Signal)

Ceramic Technology for Advanced Heat Engines Program: Semiannual Progress Report for the Period April 1, 1989, through September 30, 1989, in press.

Development of Nondestructive Evaluation Methods for Predicting Effects of Flaws on Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, C. Y. Chu, T. Hentea, and P. Rizo

Presented at 4th Ann. Conf. on *Fossil Energy Materials*, Oak Ridge, TN, May 15-17, 1990, abstract in Conf. Abstracts booklet, p. 25.

Magnetic Resonance Applications to Ceramic Processing Technology

W. A. Ellingson

INVITED TALK presented at Workshop on *Industrial Applications of Magnetic Resonance Imaging*, Charleston, MA, April 20, 1990, abstract in Workshop Agenda, p. 6.

Development of Nondestructive Evaluation Methods for Predicting Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, E.-Y Chu, T. Hentea (Purdue University-Calumet), and P. Rizo (Visiting Sci., CEA/Leti, Grenoble, France)

To be published in Proc. 4th Ann. Conf. on *Fossil Energy Materials* Oak Ridge, TN, May 15-17, 1990.

X-Ray Computed Tomographic Imaging

W. A. Ellingson, T. Hentea (Purdue University-Calumet), and R. Rizo (Visiting Scientist, CEA/Leti, Grenoble, France)

Ceramic Technology for Advanced Heat Engines Program: Semiannual Progress Report for the Period October 1, 1989, through March 30, 1990.

Development of Nondestructive Evaluation Methods for and Effects of Flaws on the Fracture Behavior of Structural Ceramics

W. A. Ellingson, J. P. Singh, C-Y Chu, N. Gopalsami, S. H. Sheen, S. L. Dieckman, T. Luethi (EMPA Laboratories), W. P. Lawrence, and T. Hentea (Purdue University-Calumet)

Fossil Energy Materials Program, Semiannual Progress Report for the Period Ending Sept. 30, 1990.

Magnetic Resonance Imaging

W. A. Ellingson

INVITED PAPER: Proc. 1989 JANNAF Nondestructive Evaluation Subcommittee Mtg., NASA Langley Research Center, Hampton, VA, May 2-4, 1989, (May-1989) pp. 37-46.

Corrosion and Mechanical Properties of Alloys in FBC and Mixed-Gas Environments

W. A. Ellingson, J. P. Singh, C-Y. Chu, N. Gopalsami, S. H. Sheen, S. L. Dieckman, T.

Luethi (EMPA Laboratories, W. P. Lawrence, and T. Hentea(Purdue University-Calumet)

Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for the Period Ending September 30, 1990, in press.

Effect of Convolution Kernels on 3-D-X-Ray CT Image Quality for Characterization of Ceramics

K. Gopalan (Purdue University-Calumet), I. I. Hentea (Purdue U.-Calumet), and W. A. Ellingson

Ceram. Eng. Sci. Proc. 11 (9-10), pp.1320-1328 (1990).

Development of NMR Imaging Probes for Advanced Ceramics

N. Gopalsami, G. A. Forster, S. L. Dieckman, W. A. Ellingson, and R. E. Botto (CHM)

Presented at *Review of Progress in Quantitative NDE*, Brunswick, ME, July 23-28, 1989.

Development of NMR Imaging Probes for Advanced Ceramics

N. Gopalsami, G. A. Forster, S. L. Dieckman, W. A. Ellingson, and R. E. Botto (CHM)

To be published in Proc. *Review of Progress in Quantitative NDE*, Brunswick, ME, July 23-28, 1989.

Nuclear Magnetic Resonance Imaging

N. Gopalsami, S. L. Dieckman, W. A. Ellingson, H. Yeh (Garrett Ceramic Components Division of Allied-Signal Aerospace Corp.), and J. P. Pollinger (Garrett/Allied Signal)

Ceramic Technology for Advanced Heat Engines Program: Semiannual Progress Report for the Period April 1, 1989, through September 30, 1989, in press.

Quantitative MRI Measurement of Binder Distributions in Green-State Ceramics

N. Gopalsami, S. L. Dieckman, W. A. Ellingson, R. E. Botto (CHM), and H. Yeh (Garrett Ceramic Components Division of Allied-Signal Aerospace Corp.)

Submitted to 17th Ann. of Progress in Quantitative NDE, Univ. of CA., San Diego, La Jolla, CA, July 15-20, 1990.

Thermal-Wave Characterization of Diffusion Coatings

N. Gopalsami and D. N. Rose (U.S. Army Tank Automotive Command, Warren, MI).

Materials Evaluation Journal 48, pp. 890-897 (May 1990)

Nuclear Magnetic Resonance Imaging

N. Gopalsami, S. L. Dieckman, W. A. Ellingson, Robert E. Botto, H. Yeh (Garrett Ceramic Components Division, Allied-Signal Aerospace Corp.), and J. P. Pollinger (Garrett/Allied-Signal)

Ceramic Technology for Advance Heat Engines Program: Semiannual Report for the Period October 1, 1989 through March 30, 1990, in press.

Quantitative MRI Measurement of Binder Distributions in Green-State Ceramics

N. Gopalsami, S. L. Dieckman, W. A. Ellingson, R. E. Botto (CHM), and H. Yeh (Garrett Ceramics Components Division, Allied-Signal Aerospace Corp.)

To be published in Proc. 17th Ann. *Review of Progress in Quantitative NDE*, San Diego, CA, July 16-20, 1990.

Digital Filtering and Image Restoration Techniques Applied to Conventional Tomographic Images

T. I. Hentea (Purdue University-Calumet), W. A. Ellingson, R. A. Roberts, and R. J. Kriz (University of Illinois Hospital, Chicago)

Presented at ASME *Pressure Vessel and Piping Conf.*, Technical Session on *Advance Inspection Techniques*, Honolulu, HI, July 23-27, 1989.

Microfocus X-Ray Computed Tomography with Application to Advanced Ceramics

T. I. Hentea (Purdue University-Calumet), W. A. Ellingson, and J. A. Morman (RAS)

Presented at the ASME *Pressure Vessel and Piping Conf.*, Technical Session on *Advance Inspection Techniques*, Honolulu, HI, July 23-27, 1989.

Parallel Computing for Rapid 3-D X-Ray CT Reconstruction and Imaging

A. Hudson (MCS), W. A. Ellingson, and K. Gopalan (Purdue University-Calumet)

Presented at 1st Intl. *Ceram. Sci. and Technol. Congress*, Anaheim, CA, October 31-November 3, 1989, abstract in Meeting Abstracts book, p. 14.

Neutron Diffraction NDE for Advanced Composites

D. S. Kupperman, S. Majumdar, and J. P. Singh

Trans. ASME 112, 198-201 (April 1990).

Characterization of Acoustic Signals from Leaking Intergranular Stress Corrosion Cracks

D. S. Kupperman, R. Carlson, R. Lanham, and W. Brewer

INVITED PAPER: Mater. Eval. (Special Issue on Leak Testing) 47(11), 1297-1300 (November 1989).

Application of Neutron Diffraction to the Characterization of Residual Thermal Strains in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}/\text{Ag}$

D. S. Kupperman, J. P. Singh, J. Faber, Jr., and R. L. Hitterman

J. Appl. Phys. 66(7), 3396-3398 (October 1, 1989).

Use of Neutron Diffraction in Determining Strains in High-Temperature Superconducting Composites

D. S. Kupperman, J. P. Singh, J. Faber, Jr., and R. L. Hitterman

Presented at 1989 Fall Materials Research Soc. Mtg., Boston, MA, November 27-December 2, 1989, abstract in Final Program and Abstracts booklet, p. 335.

Application of Neutron Diffraction NDE to High-Temperature Superconducting Composites
 D. S. Kupperman, S. P. Singh, S. Majumdar, A. C. Raptis, and R. L. Hitterman (MSD)
 To be published in *Review of Progress in Quantitative NDE*, Brunswick, ME, July 23-28, 1989.

Energy Dependent Neutron Imaging

D. S. Kupperman, R. L. Hitterman (MSD), and E. Rhodes (RAS)
 INVITED PAPER: to be published in Proc. 17th Amer. *Review of Progress in Quantitative NDE*, San Diego, CA, July 16-20, 1990.

Use of Neutron Diffraction in Determining Strains in High-Temperature Superconducting Composites

D. S. Kupperman, J. P. Singh, S. Majumdar, R. L. Hitterman (MSD), and J. Faber, Jr. (Amoco Research).
 Proc. 1989 Fall Materials Research Society Symp., Boston, MA, Vol 166, pp. 195-201 (1990).

The CERC Report, Results of the CERC Project with Recommendations for ANL Institutional Strategies in Advanced Scientific Computing

C. J. Muller (CTD), C. M. Caruthers (CTD), W. R. Cowell (MCS), W. A. Ellingson, T. F. Ewing (EP), F. M. Moszur (CTD), R. J. Harrison (CHM), D. W. Leibfritz (CTD), D. M. Malon, E. N. May (HEP), M. Minkoff (MCS), E. J. Plaskacz (DEP), J. Rowlan (CTD), D. K. Sinclair (HEP), and J. A. Volmer (CTD)
 ANL/TM 475, in press.

Metal Wastage in Fluidized-Bed Combustors

W. F. Podolski (CMT), K. J. Reimann, W. M. Swift (CMT), and E. L. Carls (CMT)
 Proc. 1989 Intl. Conf. on *Fluidized Bed Combustion*, San Francisco, CA, April 30-May 3, 1989, ed. Arnold M. Manaker, The American Society of Mechanical Engineers, New York, 1989, Vol. 2, pp. 837-846.

Practical Superconductor Development for Electrical Power Applications, Semiannual Report -- October 1989-June 1990

R. B. Poeppel, K. C. Goretta, U. Balachandran, I. Bloom (CTD), S. E. Dorris, J. T. Dusek, J. E. Emerson, K. C. Goretta, K. E. Gray (MSD), M. Hash (CTD), S. A. Johnson (CTD), R. T. Kampwirth (MSD), M. Kullberg, D. S. Kupperman, M. T. Lanagan, V. A. Maroni (CTD), R. C. McDaniel, J. H. Meiser (CTD), J. J. Picciolo, J. P. Singh, and C. A. Youngdahl
 ANL-90/25, in press.

Development of a High-Temperature Erosion Monitor for FBC Heat Exchanger Tubes

K. J. Reimann
 ANL/FE-89-4 (May, 1990).

Elastodynamic Response of Contacting Fluid and Solid Half-Spaces to a Three-Dimensional Point Load

R. A. Roberts
 Submitted to J. Wave Motion.

Advanced Research in Instrumentation and Control Technology

S. H. Sheen and A. C. Raptis

INVITED TALK to be presented at the *Advanced Research and Technology Development Direct Utilization, Instrumentation, and Diagnostics Contractors Review Mtg.*, Morgantown, WV, October 3-5, 1989.

Cavitation-Controlled Ultrasonic Agitator

S. H. Sheen, W. P. Lawrence, and A. C. Raptis

To be published in Proc. IEEE 1989 *Ultrasonics Symp.*, Montreal, Quebec, Canada, October 3-6, 1989.

BOOK REVIEW: *Ultrasonic Measurements for Process Control: Theory, Techniques, Applications*, by Lawrence C. Lynnworth (Academic Press, Inc., Harcourt Brace Jovanovich, San Diego, CA, 1990)

S. H. Sheen

INVITED REVIEW to be published in Academic Press, Inc.

Advanced Research in Instrumentation and Control Technology

Shuh-Haw Sheen and A. C. Raptis

To be presented at *Advanced Research and Technology Development Direct Utilization, Instrumentation, and Diagnostics Contractors Review Mtg.*, Pittsburgh, PA, Sept. 16-18, 1990

Advanced Research in Instrumentation and Control Technology

S. H. Sheen and A. C. Raptis

To be published in Proc. Center for Conf. Mgmt., AR&TD Contractors' Review Mtg., Pittsburgh, PA, Sept. 16-18, 1990.

Effects of Flaws on the Fracture Behavior of Structural Ceramics

J. P. Singh, C. Y. Chu, R. A. Roberts, W. A. Ellingson, and A. L. Bosak

INVITED TALK presented at Third Ann. *Fossil Energy Materials Program Contractors' Conf.*, Oak Ridge, TN, August 8-10, 1989; abstract in Program and Abstracts booklet, pp. 23-24.

Fracture Behavior and Nondestructive Evaluation of Si_3N_4 and Its Composites

J. P. Singh, C. Y. Chu, A. Wagh (University of the West Indies), R. A. Roberts (Ames Laboratory), and W. A. Ellingson

To be presented at the 92nd Ann. Mtg. of the Am. Ceram. Soc., Dallas, TX, April 22-26, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, and R. L. Hitterman

To be presented at the Intl. Conf. on *Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

Determination of Internal Strains in High-Temperature Superconductor Composites by Intense Pulsed Neutron Source

J. P. Singh, D. S. Kupperman, S. Majumdar, R. L. Hitterman (MSD), and D. W. Schroeder
 INVITED PAPER to be published in *Proc. Intl. Conf. on Micromechanics of Failure of Quasi-Brittle Materials*, Albuquerque, NM, June 7-8, 1990.

Strength/Grain-Size Relationships and Internal Stresses in YBCO Superconductors

J. P. Singh, R. Guttschow, D. S. Kupperman, J. T. Dusek, and R. B. Poeppel
 To be presented at 3rd Intl. Symp. on *High-Temp. Superconductors: Processing and Microstructure Property Relationships*, The Metallurgical Society Mtg. and Exhibition, New Orleans, LA, Feb. 17-21, 1991.

Proton Nuclear Magnetic Resonance Characterization of Binder Distributions in Si_3N_4 Ceramics

P. S. Wong, W. A. Ellingson, R. E. Botto (CHM), H. C. Yeh (Garrett Ceramic Components Division, Allied-Signal Aerospace Company), and J. P. Pollinger (Garrett/Allied-Signal)
Proc. 3rd Intl. Symp. on Ceramic Materials and Components for Engines, Las Vegas, NV, November 27-30, 1988, ed. V. J. Tennery, Plenum Press, New York, 1989, Vol. 32, pp. 1147-1158.

Patents

High Temperature Ultrasonic Testing of Materials for Internal Flaws

David S. Kupperman and Mel Linzer (National Institute of Standards and Technology)
 U. S. Patent No. 4,898,034 awarded February 6, 1990.

Neutron Apparatus for Measuring Strain in Composites

David S. Kupperman, S. Majumdar, John Faber, Jr. (MSD), and J. P. Singh
 U.S. Patent No. 4,959,548 awarded September 25, 1990.

Scanning Ultrasonic Probe

D. S. Kupperman and K. J. Reimann
 U. S. Patent No. 4,361,044 awarded November 30, 1982.

High Intensity X-Ray Source Using Liquid Gallium Target

Robert K. Smither (MSD), Gordon S. Knapp (Surface Science Laboratories, Inc.), Edwin M. Westbrook (BIM), and George A. Forster
 U.S. Patent No. 4,953,191 awarded September 28, 1990.

Transportation of Hazardous Materials

Section Manager: G. F. Popper

Principal Investigators: R. D. Carison, R. R. Fabian, K. A. Gablin, J. J. Oras,

F. G. Prohammer, V. L. Shah, P. Turula

Other Staff: T. R. Bump,¹ E. M. Pennington, D. T. Raske, Z. B. Wang, S. A. Zawadzki¹

Secretary: J. L. Fisher

The Transportation of Hazardous Materials Section primarily provides direct technical assistance to DOE in reviewing Safety Analysis Reports for Packaging (SARPs) of nuclear waste shipping packages for compliance with DOE Orders and with NRC and Department of Transportation regulations. In addition, the Section provides technical assistance to DOE on a variety of generic waste management and transportation issues, including the review of Facility Conceptual Design Reports and Safety Analysis Reports for DOE waste handling and other facilities.

SARP Review Group

This group operates independently of other Section programs and comprises a multi-divisional, dedicated staff that includes the disciplines necessary to review the entire range of information provided in a SARP. When received by DOE from an applicant, each SARP is assigned a docket number. On the average, more than 20 dockets are open at any given time. The SARP is usually a voluminous document that describes the packaging technically and justifies why the packaging meets all applicable regulations.

The SARP consists of nine chapters: General Information and Drawings; Structural; Thermal; Containment; Shielding; Criticality; Operating Procedure; Acceptance Tests and Maintenance Program; and Quality Assurance. Some of the review activities are described below.

Structural

The structural review of a SARP is primarily concerned with determining whether the packaging performance meets the requirements contained in the federal regulations issued by the NRC. To predict packaging performance, various structural computations are carried out. For example, studies are made of deformations due to impact in regulatory accident drop events and of seal surface movements due to thermal gradients. During the review, an independent analysis calculates and evaluates the expected performance of the packaging under selected loading conditions. To produce meaningful results for complex packagings, computer solutions of finite-element models, using a dynamic analysis code, are essential.

¹Part-time staff.

Mainframe computer codes such as ANSYS, DYNA, or ADINA are available for such analyses. To perform nonlinear analysis of structures subjected to impact and thermal stresses, the SARP Review Group selected the ANSYS code running on a SUN workstation, for several reasons. First, the ANSYS code is used very extensively in the nuclear engineering community and therefore has been thoroughly tested, benchmarked, and documented; the ANSYS code element formulations and solution techniques are generally accepted by regulators as being correct. Second, use of ANSYS on the SUN has been cost-effective because the code is leased on a monthly basis and runs on division-owned equipment. Thus, even though individual runs may be very long, computing costs do not escalate. However, because ANSYS is limited to the "implicit" solution method for structural dynamics problems, impractical solution times are encountered for problems in which the impact deformations must be modeled in greater detail. For this reason, codes that use the "explicit" integration method are being considered.

To extend the capabilities of ANSYS to cask configurations that use lead for shielding, a viscoplastic constitutive material model was developed and added to the standard ANSYS code. Realistic modeling of lead behavior is particularly important because the lead shielding could shift during a hypothetical accidental drop impact, resulting in a possible streaming path for radiation. ANSYS accommodates specialized material-property models by accepting a user-supplied subroutine that defines a specific form of nonlinear behavior. The material model developed for lead takes into account strain rate sensitivity, which is the increase in resistance to deformation that many materials exhibit under rapid loading. An appropriate mathematical formulation was selected and programmed as a user-supplied subroutine to include the strain rate effect at each time-step as the element material stresses are computed.

Displacement at the center of a spherical shell segment: theoretical vs. results of elasto-viscoplastic material model

*Displacement produced by a thermal gradient
in a cask subjected to fire*

The proper behavior of this new material model was established by (1) running several simple models for which theoretical results are published, including a spherical shell segment under uniform pressure; and (2) by modeling several casks for which experimental impact test data can be obtained from open literature. The computer-generated results for permanent deformations of the lead shielding were within 10% of the corresponding deformations measured in the tests reported in the literature. This material-model development and verification work was documented and published.

Both the ANSYS code on the SUN System and a commercially distributed linear finite-element code installed on a PC were used to model a spent fuel cask described in a SARP submitted to DOE for certification. The major concern investigated for this application was the behavior of the cask seal when the entire package is subjected to a hypothetical thermal event, as required by Federal Regulations. The analysis carried out by the SARP Review Group indicated that the heat transferred directly to the cask body through a circumferential gap in the thermal shield was sufficient to result in a gradient in the cask body large enough to cause separation of the cask lid from the flange of the cask body. As a result, the ability of the cask to maintain federally mandated radioactive material leakage rate limits was in question. The thermal shield of the cask was eventually redesigned to eliminate this circumferential gap.

Materials

The purpose of the materials review is to provide an assessment of the materials used in the overall construction of the packaging. The objective is to verify that the materials loadings expected during both normal and hypothetical transport accident conditions. Although no specific acceptance criteria exists for packaging materials, all of the materials used for construction must be sufficiently characterized to allow a technical evaluation of

the packaging. The structural materials important to safety are usually selected from the those listed in the ASME Boiler and Pressure Vessel Code, and the Code properties are used in the packaging design. Other authoritative standards, such as ASTM, manufacturer data, and qualification by testing are used for materials not covered by the Code. Materials not covered by authoritative standards must be adequately characterized and documented to establish their quality and suitability for the intended service. This includes mechanical and physical properties, plus the effects of the fabrication processes on subsequent behavior.

Thermal

The thermal review evaluates the thermal operating characteristics and performance of the packaging under normal and hypothetical transport accident conditions, taking into account the extreme environmental conditions, minimum and maximum decay heat loads, and damage caused by the drop and puncture tests, as specified in Code of Federal Regulations (CFR), Title 10, Part 71. The review also includes confirmatory analyses; comparison of the analyses results with allowable limits of temperature, pressure, and thermal stresses for the packaging components; and determination of the effect of thermal performance on the structural, containment, and shielding areas of the packaging.

To determine that a package under review complies with the CFR under all conditions of transport, the confirmatory analyses are focused on modeling and evaluating package performance under worst-case conditions. Normally, worst-case scenarios are too complex to model with any degree of certainty; thus, analyses are done for the bounding cases. An example of one bounding-case analysis performed recently, using the HEATING6 module of the SCALE Computer Code, is described below as an illustration. The SARP Review Group selected HEATING6 because the module is designed specifically for thermal analysis of nuclear shipping casks. Furthermore, the code has been thoroughly tested on a set of casklike problems, compared with other thermal analysis codes such as TRUMP, TEMPEST, Q/TRAN, and CINDA-3G, and well-documented.

For a packaging designed to ship americium or plutonium, the outer casing consists of an aluminum tank filled with water-extended polyester (WEP) for shielding. A flanged stainless steel secondary containment vessel was mounted axially in the center of the tank. The primary containment vessel was a seal-welded cylinder containing the americium or plutonium powders retained inside a handling or product canister.

The structural review staff needed to know the maximum temperature of the primary containment vessel during the hypothetical accident thermal event. The information was necessary to determine whether the stresses at the seal-weld locations were within the allowable limits and to ensure that the seal welds would not fail and permit release of any radioactive contents.

The initial analysis of the packaging for the hypothetical accident thermal event showed that the outer casing can definitely provide thermal protection to the primary containment vessel for a minimum of 10 min before the casing may begin to melt. Because the melting behavior of the outer casing for the remaining period of the required 30 min thermal event cannot be modeled with any certainty, two bounding analyses were

performed. In one analysis, the packaging without the outer casing was assumed exposed to a 1475°F environment for the full 30-min thermal event. The second analysis was performed in two steps. First, the packaging with the outer casing was considered to be exposed to a 1475°F environment for a period of 10 min. For the remaining 20 min of the thermal event, the outer casing was assumed to have completely melted away.

The maximum temperatures of the primary containment vessel for both cases are shown in the figure on the next page. The bounding analyses show that even though there is a significant difference in temperatures between the two cases at a time equal to 10 min, this difference decreases rapidly. By the end of the 30-min thermal event, the temperatures for both cases are nearly equal. In other words, the presence of the outer casing has no effect on the final maximum temperature of the primary containment vessel. The dotted lines in the figure are included only to show how the temperatures will increase and attain their asymptotic values beyond the 30-min test duration.

Containment

Areas of review for containment evaluation are the (1) integrity of the containment boundary, (2) radioactive leak rate requirements for normal and hypothetical accident conditions, and (3) special double-containment requirements for plutonium shipments. Containment evaluation is intimately connected with the structural and thermal analyses for input on the environment and integrity of the containment boundary.

A special issue is the generation of hydrogen gas from radiolysis of hydrogenous materials in shipping packages used for transporting radioactive materials. The hydrogen gas can jeopardize package performance by increasing the maximum operating pressure above the allowable design pressure and/or by forming an explosive mixture, detonation of which could destroy the containment. A calculational procedure was implemented by an EPRI computer code to predict the concentration of hydrogen gas present inside a waste container after a specified storage duration. The calculational methodology determines the total dose absorbed by the waste as a function of curie loading, waste density, and container geometry; it then calculates hydrogen gas generation as a function of absorbed dose and a predetermined gas generation constant. The computer code was benchmarked by EPRI using actual gas measurements from liners containing dewatered resin waste from the cleanup operations at Three Mile Island Unit 2. On the average, the predicted hydrogen gas concentrations calculated by the code were within 20% of the hydrogen concentrations measured when the liners were vented before shipment.

To extend the usefulness of the computer code to cask contents encountered by ANL during the transport of radioactive waste, additional radionuclides are being incorporated in the code by ANL as the need arises. Before the code can be used with confidence, the results must be benchmarked for each radionuclide to ensure the use of the appropriate radionuclide and gas generation constant for the hydrogenous material being considered. The plutonium radionuclides have been benchmarked with measurements of two separate containers, and the predicted hydrogen gas concentrations three months after cask closure

*Numerical model
with outer casing*

*Numerical model
without outer casing*

Temperature of the primary containment vessel

were within 10% of the measured hydrogen gas concentrations reported in the open literature. The code was then used to predict hydrogen gas generation in another packaging with a polyethylene liner. The code predicted 98% hydrogen gas concentration one month after cask closure. Because this does not seem reasonable, the calculational procedure is being examined to find the reason. A possible explanation is the unrealistic assumption that all of the alpha, beta, gamma, and neutron energy is absorbed by the thin liner of plastic.

Shielding

The purpose of the shielding review is to verify that the packaging design meets the DOE requirements that the dose rate is less than 200 mrem/hr at the package surface and less than 10 mrem/hr at 2 m from the package surface for normal conditions of transport and less than 1000 mrem/hr at 1 m from the package surface during hypothetical transport accident conditions. These DOE requirements are the same as the NRC regulations in 10 CFR 71. Independent confirmatory analyses are performed for each packaging with modules of the SCALE computer code, the ORIGEN code, and, for quick estimates, the MICROSIELD code.

Using the PC-based MICROSIELD code, we estimated the effectiveness of the shielding for a radioactive cobalt sample to be shipped in the Cobalt Irradiator Package. The 631-curie source was modeled as a sphere surrounded by a spherical steel shell with a 15-in. radius, as shown in the figure below. The results showed a surface dose rate of 3 mrem/hr, which is well below the 200-mrem/hr limit allowed for normal transport conditions.

Model of cobalt irradiator

Criticality

The criticality review ensures that a packaging remains subcritical with a $k_{eff} < 0.95$ during both normal and hypothetical transport accident conditions. A criticality review was performed on an amendment to the Certificate of Compliance for the Model RA-3 shipping packages when Pennsylvania State University planned to ship Pathfinder fuel assemblies. These fuel assemblies were of a slightly different construction and of a slightly higher enrichment than those covered by the original Certificate of Compliance.

Package loading and computer modeling of the fuel elements are shown schematically in the figure below. The 6-ft-long fuel element, whose top view is shown first, is composed of six fuel rods clustered around a central poison rod (a). Twenty-two fuel elements are fitted into a 5-in. steel pipe (b), and two of these pipes form a package (c). All of the fuel and poison rods within each pipe were modeled for computational purposes as a square array of fuel and poison rods (d). For conservatism, care is exercised to maintain a higher ratio of fuel to poison rods in the model than is actually the case. The two steel pipes are enclosed in a steel container (c), which in turn is embedded in a wooden box, and six such wooden boxes are included in a shipment. Federal regulations require that during normal transport conditions, five times the number of shipments must remain subcritical when reflected on all sides by water. The array of thirty wooden units is depicted as three units in (e). For a Fissile Class II shipment during hypothetical transport accident conditions, twice the number of damaged packages must be subcritical when reflected on all sides by water. The damaged condition was modeled with the wooden outer boxes removed, allowing a closer packing of the steel containers than under normal conditions (f).

Computer modeling of pathfinder fuel assemblies

The confirmatory analysis to verify the criticality safety under normal and hypothetical transport accident conditions was made with the KENO Va module of the SCALE Computer Code. Below is a summary of the main results, where the k_{eff} values shown include two standard deviations:

Condition	k_{eff}
30 Wooden Units	0.429
Infinite Array	0.832
Hypothetical Accident	0.917

The first two entries in the table are for the normal transport condition. The infinite array was calculated with none of the poison rods present, to determine the margin of safety. A k_{eff} of less than 0.95 is considered to be subcritical. The original Certificate of Compliance allowed Fissile Class I shipments, which means that up to 250 packages could be on the road at any one time. Because the confirmatory analysis showed that 250 damaged packages would not remain subcritical, the shipments had to be made as Fissile Class II, which allows only two packages on the road at one time, a very serious but necessary restriction.

Based on the ANL Technical Review Report, DOE submitted a Safety Evaluation Report to the NRC. After a short NRC review, the Certificate of Compliance for the Model RA-3 shipping packages was amended to include the Pathfinder fuel assemblies with a Fissile Class II classification. The SARP Review Group was informed verbally by DOE that the NRC was very complimentary of the ANL review analysis.

Quality Assurance

The quality assurance review verifies that all of the applicable QA requirements for the packaging are contained in the SARP. The QA information should include provisions for control of the design, procurement, fabrication, testing, operations, and maintenance activities related to the packaging identified in the QA plan. Federal Regulation 10 CFR Part 71 is considered to be the regulating document in establishing requirements for the QA plan. However, NRC Regulatory Guide 7.10 (Establishing Quality Assurance Programs for Packaging Used in the Transport of Radioactive Material) and ANSI/ASME NQA-1 (Quality Assurance Program Requirements for Nuclear Facilities) are considered to be guidance documents for the implementation of 10 CFR Part 71 QA requirements.

To provide training for the SARP applicant on determining the QA requirements that apply to a particular packaging, select members of the ANL SARP Review Group, along with the DOE-HQ sponsor and two members from ANL-West Quality Assurance, conduct a two-and-one-half-day QA Workshop for SARPs at various DOE field office sites. The objective of the workshop is to discuss a proven method or process for determining which QA requirements from NRC Regulatory Guide 7.10 and ANSI/ASME NQA-1 apply to a specific

packaging for compliance with the QA requirements in 10 CFR Part 71. During the past four years, ANL has conducted 16 QA workshops at DOE field office sites, with a total of 350 DOE and DOE contractor personnel attending. The workshop provides the applicant with valuable information for developing, establishing, and implementing an effective QA plan for a specific packaging.

Generic Waste Management and Transportation Technical Support

The tasks in this effort are directed toward achieving specific objectives defined by the DOE Transportation Management and Waste Operations Divisions. Present task areas include the production and distribution of public information films and films for DOE audiences. In addition, Conceptual Design Reports and Safety Analysis Reports for waste handling facilities are being reviewed for compliance with technical criteria and DOE Orders.

Information Films and Videos

Films and videos are an entertaining and effective way to provide information to the public and training participants on transportation issues.

Training and public information films are being made for DOE's Transportation Management Division. The major early use for these films was for training purposes, as well as for explaining—primarily to state and local government representatives—how radioactive material (RAM) is shipped. In early FY 90, emphasis was placed on achieving wider distribution to local emergency and law enforcement personnel for use in their training programs. Another goal was to make a film available to students, civic groups, and other members of the public. This effort resulted in a very successful distribution program through Modern Talking Pictures, both through bookings in classrooms and through broadcast on cable television.

Distribution of the *Transportation of Radioactive and Other Hazardous Material* film by Modern Talking Pictures began in February 1990. The 17-1/2-min film/videotape made by ANL for DOE covers four main areas. First, there is an introduction to the shipping of hazardous materials in general and of radioactive materials in particular. Then an explanation of the nature and forms of radioactivity and of radioactive materials is given. An overview of the general methods and precautions used in transporting radioactive materials is described. And finally, there is an introduction to the extraordinary containers used to ship the highest-level radioactive materials. The Modern Talking Pictures certification of showing for the past 10 months through the end of November 1990 indicates that 174,000 students have viewed the film in classrooms. Furthermore, the film is currently scheduled to be shown 1,800 times during the current school year ending in May 1991, and new bookings are being obtained every month. Collateral material consisting of a short teachers guide and the DOE booklet DOE/DP-0064 *Transportation of Radioactive Materials ... Answers to your Questions*, are also included to complete the program for distribution to schools.

The number of cable television showings has been exceptional. The Modern Talking Pictures certification of telecasts indicate that 10,750,000 people have viewed the film in

their homes through November 1990. A number of stations have shown this film over and over again, which indicates a strong viewer interest. Four nationwide showings have been made via the cable network station The Learning Channel.

Conceptual Design Report and Safety Analysis Report Reviews

As an integral part of the DOE five-year Environmental Restoration and Waste Management Plan, several facility upgrades and new facilities are planned. One principal task of the Section is to provide direct technical support to DOE-HQ by performing independent

Facilities reviewed during FY 90

Facility Name	Estimated Completed Facility Cost (\$)	Estimated Operating Cost (\$/yr)
TRU-Waste Treatment Storage Facility Idaho National Engineering Laboratory Site	94,000,000	4,000,000
Waste Receiving & Processing Facility Hanford Site	52,000,000	4,000,000
High-Level Waste Tank Farm Upgrade Idaho National Engineering Laboratory Site	264,000,000	---
Waste Handling & Packaging Plant Oak Ridge National Laboratory Site	230,000,000	9,000,000
High-Level Waste Removal from Filled Waste Tanks Savannah River Site	105,000,000	---
Inter-Area Line Upgrade Savannah River Site	20,000,000	---
TOTAL	765,000,000	17,000,000

independent reviews of the Conceptual Design Reports (CDRs) and Safety Analysis Reports (SARs) for some of the new facilities and facility upgrades (see table). ANL is not directly involved in most of the waste disposal sites or waste handling facilities and is therefore in an excellent position to conduct the independent reviews required.

The CDR independent reviews are conducted through the use of various relevant engineering and scientific disciplines. The review evaluates the functional design to ensure that the selected criteria are reasonable and appropriate for the type of facility being proposed; that the appropriate design standards are evoked; that the waste streams are adequately characterized; and that the acceptance criteria for disposal and transport are defined in sufficient detail. Weaknesses are identified in the form of written reports or questions. Use of such questions to clarify and enhance reported information is a technique used satisfactorily in the certification process for shipping packaging for radioactive material.

In addition, the CDRs must be reviewed for compliance with DOE Orders; 4700.1 Project Management System, 6430.1A General Design Criteria, 5480.2A Radioactive Waste Management, 5700.6B Quality Assurance, and others referenced by these orders. Compliance with the CFR 40 (National Environmental Policy Act, Resource Conservation and Recovery Act, Clean Air Act, Clean Water Act) is also evaluated. All elements in the long list of DOE Orders, federal, and state regulations may not be addressed in detail during the Conceptual Design phase. However, the Conceptual Design Report must provide confidence that a plan exists to comply with these documents and that the costs associated with compliance are taken into consideration during this phase.

Similar techniques are used for reviewing Safety Analysis Reports (SARs) for waste operation facilities. During FY 91, reviews are being conducted of the Hazardous Waste Management Facilities at Lawrence Livermore National Laboratory and the Toxic Substance Control Act Incinerator K-25 Plant at Oak Ridge National Laboratory.

Recent Work by the Transportation of Hazardous Materials Section

Publications

Characterization of Acoustic Signals from Leaking Intergranular Stress Corrosion Cracks

D. S. Kupperman, R. Carlson, R. Lanham, and W. Brewer

**INVITED PAPER: Mater. Eval. (Special Issue on Leak Testing) 47(11), 1297-1300
(November 1989).**

Appendixes

Appendix A: Regular MCT Employees

Administration

Staff R. W. Weeks, Division Director
 W. J. Shack, Associate Division Director
 R. A. Valentin, Associate Division Director
 W. H. Livernash, Building Manager, 212
 B. H. Malak, Financial Administration
 C. A. Malefy, Technical Editor
 A. C. Smith, Jr., Deputy Facilities Engineer, 212
 D. L. Telfer, Staff Assistant

Salaried B. K. Baudino
 J. L. Donahue

Materials Technology

	Ceramics	Corrosion	Mechanics of Materials
<i>Staff</i>	R. B. Poeppel U. Balachandran S. E. Dorris K. C. Goretta M. T. Lanagan P. S. Matya J. J. Picciolo J. P. Singh C. A. Youngdahl	T. F. Kassner O. K. Chopra H. M. Chung A. B. Hull B. A. Loomis K. Natesan J. H. Park W. E. Ruther W. K. Soppet	D. R. Diercks M. C. Billone P. E. Domagala+ A. M. Hassanein P. Hicks** C. C. Lin** S. Majumdar J. Y. Park J. Rest A. Stojimirovic** H. R. Thresh T. Wiencek S. A. Zawadzki
<i>Salaried</i>			W. F. Burke D. R. Schmitt J. R. Summers
<i>Technicians</i>	J. E. Emerson R. L. McDaniel	R. W. Clark G. M. Dragel D. L. Rink L. J. Nowicki	T. M. Galvin C. F. Konicek D. R. Perkins S. L. Phillips F. E. Soppet G. J. Talaber J. C. Tezak J. A. Zic
<i>Secretary</i>	S. M. Hagamann*	S. M. Hagamann*	P. J. Peterson

	Tribology	Irradiation Performance
<i>Staff</i>	F. A. Nichols O. Ajayi** D. E. Busch R. A. Erck A. Erdemir G. R. Fenske J. H. Hsieh** A. I. Michaels	L. A. Nelmark A. B. Cohen D. A. Donahue A. G. Hins Y. Y. Liu J. E. Sanecki H. C. Tsai
<i>Salaried</i>		W. Kettman F. Pausche
<i>Technicians</i>	R. H. Lee	D. J. Evans D. O. Pushis F. E. Savole K. E. Stair
<i>Secretary</i>	D. K. Moores	E. L. Hartig

*Assigned to more than one section.

**Postdoctoral appointment.

+Term appointment.

Components Technology

	Superconductivity Applications	Thermal and Mechanical Sciences	Analytical Thermal- Hydraulics
<i>Staff</i>	J. R. Hull Y. S. Cha J. L. He** (RE) T. M. Mulcahy K. L. Uherka	M. W. Wambsganss S. S. Chen S. U. Choi J. A. Jendrzeczyk K. E. Kasza	W. T. Sha F. C. Chang** T. H. Chien H. M. Domanus R. C. Schmitt
<i>Technicians</i>		D. M. Engel R. K. Smith	
<i>Secretary</i>	J. A. Stephens*	J. A. Stephens*	S. A. Moll
	Instrumentation and NDE	Transportation of Hazardous Materials	
<i>Staff</i>	A. C. Raptis S. L. Dieckman+ W. A. Ellingson G. A. Forster N. Gopalsami E. R. Koehl D. S. Kupperman W. P. Lawrence S. H. Sheen	G. F. Popper T. R. Bump R. D. Carlson K. Gablin+ J. J. Oras, Jr. D. T. Raske+ V. L. Shah P. Turula Z. B. Wang** R. R. Fabian (QES) E. M. Pennington (EP) F. G. Prohammer (RAS) A. B. Rothman (RAS)	
<i>Salaried</i>	W. E. Brewer		
<i>Technicians</i>	R. N. Lanham		
<i>Secretary</i>	N. M. Heeg	J. L. Fisher	

*Assigned to more than one section.

**Postdoctoral appointment.

+Term appointment.

Appendix B: Recent and Current Interactions between MCT and Industry

Organization	MCT Personnel	Subject of Collaboration	Duration of Collaboration
ABB/ Combustion Engineering	J. R. Hull, K. L. Uherka, T. M. Kuzay	Small magnetic energy storage devices using high- T_c superconductors	1989-90
Adiabatics, Inc.	F. A. Nichols, G. R. Fenske	Low-friction and -wear coating	Ongoing
ADEC	S. H. Sheen, W. W. Lawrence	Heatmeter testing	Ongoing
Alcoa	W. A. Ellingson	Nondestructive evaluation of ceramics	Ongoing
Allied-Signal Aerospace Co.	S. Majumdar	Stress analysis of mono- lithic solid oxide fuel cell	Ongoing
Allied-Signal Engineered Materials	J. P. Singh	Structural ceramics	Ongoing
	D. S. Kupperman	Residual stress in composites	Ongoing
	R. B. Poeppel, U. Balachandran, S. E. Dorris	Solid oxide fuel cells	Ongoing
American Science & Engineering	W. A. Ellingson	X-ray computed tomographic imaging of fuel cell ceramics	Ongoing
American Technology Corp.	A. B. Hull	Mineral beneficiation	Ongoing
Amoco	O. K. Chopra	Embrittlement of aged cast stainless steels	Ongoing
	H. M. Chung	Failure analysis of stainless steel	Ongoing
Aptech Engineering	W. J. Shack, T. F. Kassner	BWR water chemistry	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Astronautics Corp. of America	K. Uherka	Evaluation of industrial magnetic heat pumps/ refrigerators using superconducting magnets	1988-90
ATEK Metals Center, Inc.	U. Balachandran	Hot extrusion of high-temperature superconductor	Ongoing
Babcock & Wilcox	K. Natesan	Weldments and alloys for FBC and MHD tests	Ongoing
	D. R. Diercks	Characterization of material from TMI-2 pressure vessel	Ongoing
	T. C. Wiencek	Development of fuel for Advanced Neutron Source	Ongoing
Battelle Columbus Division	K. Natesan	Corrosion-resistant alloys for fossil systems	Ongoing
	J. Rest, P. E. Domagala	Fission product chemistry	Ongoing
Benchmark Structural Ceramics Corp.	J. P. Singh	Structural ceramics/composites	Ongoing
BioImaging Research	W. A. Ellingson	X-ray computed tomographic imaging of structural ceramics	Ongoing
	S. L. Dieckman, N. Gopalsami	NMR imaging instrumentation design	Ongoing
BIRL	F. A. Nichols	Hard coatings for high-temperature wear resistance	Ongoing
Borg Warner	W. A. Ellingson	Nondestructive evaluation of ceramic-metal joining	Ongoing
Bronson & Bratton	R. B. Poeppel J. T. Dusek	Fuel cell fabrication	Ongoing
Burton Technologies, Inc.	F. A. Nichols	Low-friction materials	1989-90

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Caterpillar	D. S. Kupperman	NDE of tractor tracks	Ongoing
	W. T. Sha, H. Domanus, R. Schmitt	Casting Modeling Consortium	1989-93
	F. A. Nichols, G. R. Fenske	Wear-resistant coatings for engine components	Ongoing
CBI-SC	T. M. Kuzay	High-temperature super- conducting magnetic energy storage	1989-90
CEGB (UK)	O. K. Chopra, H. M. Chung	Exchange of aging data and specimens	Ongoing
Ceracon	J. R. Hull	Current lead fabrication	Ongoing
Cerca (France)	G. L. Hofman	Research reactor fuels technology transfer	Ongoing
C-K Engineer- ing	F. A. Nichols, A. I. Michaels	Low-friction components for engines	1989-90
Combustion Engineering	D. S. Kupperman	NDE	Ongoing
	A. R. Brunsvold	Development program: assessment of modular high-temperature gas reactor-steam generator	Ongoing
	A. C. Raptis	Process instrumentation	Ongoing
	H. M. Chung	Aging of Inconel alloys and cast stainless steel	Ongoing
Commonwealth Edison Co.	W. J. Shack, T. F. Kassner	Effects of BWR water chemis- try on stress corrosion cracking of reactor materials	Ongoing
	D. R. Diercks	Analysis of failed power plant components	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Computech	F. A. Nichols	Tribology-piston rings-modeling	1989-90
Consolidated Edison of New York	D. S. Kupperman	Acoustic detection of leaks in steam pipes	Ongoing
CPS Superconductor	U. Balachandran	Synthesis and fabrication of ceramic superconductors	Ongoing
Cummins Diesel	F. A. Nichols	Ceramics and coatings for adiabatic diesels	Ongoing
Deere & Co.	F. A. Nichols	Tribology-lubrication-modeling	Ongoing
Dicronite Corp.	F. A. Nichols, G. R. Fenske	Low-friction solid lubricants	1989-90
Dow Chemical Co.	F. A. Nichols, G. R. Fenske	Low-friction coatings for plastic components	Ongoing
	S. L. Dieckman	NMR imaging of polymer blends	Ongoing
Dow Corning	J. P. Singh, D. S. Kupperman	Ceramic composites	Ongoing
DuPont	W. A. Ellingson	Nondestructive evaluation of structural ceramics	Ongoing
	S. E. Dorris, M. T. Lanagan	Development of high-temperature superconducting coils	Ongoing
EDF (France)	O. K. Chopra	Exchange of data on aging degradation of cast stainless steel	Ongoing
EG&G	J. Rest	Severe fuel damage in LWRs	Ongoing
Electric Power Research Institute	W. J. Shack, T. F. Kassner	Exchange of stress corrosion cracking information	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Electric Power Research Institute	C. A. Kot, M. G. Srinivasan, B. J. Hsieh	Validation of seismic calculation methods	Ongoing
	T. F. Kassner	Guidelines for BWR water chemistry	Ongoing
	K. Natesan	Materials for gasification and fluidized bed combustion	Ongoing
	B. A. Loomis	Fusion materials	Ongoing
	C. A. Youngdahl	FBC erosion probe and limits	Ongoing
	H. M. Chung	Irradiation-assisted stress corrosion cracking	Ongoing
	K. E. Kasza	Ice-slurry field testing at Northern States Power Co.	Ongoing
Environmental Research Institute of Michigan	D. S. Kupperman, S. Majumdar, J. P. Singh, S. E. Dorris	Fabrication and evaluation of β'' -alumina electrolyte	Ongoing
Exxon Oil Co.	H. M. Chung	Failure analysis of stainless steel	Ongoing
Foote Mineral Company	R. B. Poeppel	Evaluation of fusion-solid breeder blanket materials	Ongoing
Foster Wheeler Energy Corp.	K. Natesan	Weldments and claddings for FBC tests	Ongoing
	A. C. Raptis	NDE-cooperative proposal	Ongoing
Framatome (France)	O. K. Chopra	Exchange of data on aging degradation of cast stainless steel	Ongoing
	W. A. Ellingson	Nondestructive evaluation of structural ceramics	Ongoing
General Atomics	U. Balachandran	Fabrication of superconductors	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
General Dynamics	M. T. Lanagan, K. C. Goretta	High-temperature superconducting coil quenching	Ongoing
General Electric	W. J. Shack, T. F. Kassner, W. E. Ruther, P. S. Matya	Exchange of stress corrosion cracking data on BWR materials	Ongoing
	H. M. Chung, J. E. Sanecki	Irradiation-assisted stress corrosion	Ongoing
	D. S. Kupperman	Measurement of residual strain in metal matrix composites	Ongoing
	R. A. Jaross, R. A. Holtz	Development of high-temperature electrical insulation for EM pump	1989-90
	M. C. Billone	IFR; PRISM reactor design	Ongoing
General Motors Electromotive Division	T. M. Mulcahy, J. R. Hull	Maglev systems	1989-90
GTE Laboratories	W. A. Ellingson, J. P. Singh	Nondestructive evaluation of structural ceramics	Ongoing
GTE-Wesco Division	W. A. Ellingson	Nondestructive evaluation of structural ceramics	Ongoing
Halden Project (Norway)	H. M. Chung	Irradiation of steel components	Ongoing
Harwell Technology (U.K.)	H. M. Chung	Thermal aging and irradiation-assisted stress corrosion	Ongoing
Heat Transfer Research, Inc.	M. W. Wambsganss	Heat exchanger tube vibrations	Ongoing
Hitachi (Japan)	H. M. Chung	Thermal aging and stress corrosion	Ongoing
HiTc Superconco	C. A. Youngdahl	Filamentary wires and contacts	Ongoing
I.I.T.R.I.	A. C. Raptis	Sensors (collaborative proposal)	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
I.I.T.R.I.	N. Gopalsami	Millimeter-wave radiometer	Ongoing
ITT Fluid Handling (Bell & Gossett)	K. E. Kasza, S. Choi	Thermal system component tests with advanced energy transmission fluids	Ongoing
Jack R. Benjamine Associates	C. A. Kot	Validation of seismic calculation methods (project consultant)	Ongoing
LIXI, Inc.	W. A. Ellingson	Real-time X-ray imaging of ceramics	Ongoing
Long Island Lighting Co.	D. R. Diercks	Examination of nuclear reactor components	1991
Magneco/Metrel	J. P. Singh, R. B. Poeppel	Refractory development	Ongoing
Magnetek	M. T. Lanagan	Processing of high-T _c superconductors	Ongoing
Magnetrol International	N. Gopalsami	Acoustic level measurements	Ongoing
Mallinckrodt Institute of Radiology	W. A. Ellingson	X-ray computed tomography and nuclear magnetic resonance imaging of structural ceramics	Ongoing
Massachusetts General Hospital	W. A. Ellingson	Nuclear magnetic resonance imaging of ceramics	Ongoing
McDonnell-Douglas Astronautics Co.	S. Majumdar, A. Hassenein, M. C. Billone	Fusion reactor design studies	Ongoing
MEA, Ltd.	K. J. Reimann	Nondestructive evaluation at high temperatures	Ongoing
Meyer Mfg. Corp.	T. M. Kuzay	Nitrogen loop test bed	Ongoing
Mitsubishi (Japan)	H. M. Chung	Aging of steels	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Nalco Chemical Co.	K. C. Goretta	Corrosion studies of high-temperature superconductors	Ongoing
National Lamination	U. Balachandran	Development of prototype transformer using high-temperature superconductors	Ongoing
NFD (Japan)	H. M. Chung	PCI failure and fuel rod performance	Ongoing
NKK (Japan)	K. Natesan	Irradiation-assisted stress corrosion	Ongoing
Northwest Utilities Service Company	M. W. Wambsganss, S. S. Chen	Heat exchanger tube vibrations	1988-90
Norton Ceramic Co.	J. P. Singh	Structural ceramics	Ongoing
	W. A. Ellingson	Nondestructive evaluation of structural ceramics	Ongoing
NSP Utility	K. E. Kasza, S. U. Choi	Field testing of ice slurries	Ongoing
Nukem (Germany)	G. L. Hofman	Research reactor fuel development	Ongoing
Phillips Petroleum	S. L. Dieckman	NMR imaging of polymers	Ongoing
PNC (Japan)	L. A. Nelmark, H. C. Tsai, Y. Y. Liu	Joint LMFBR fuel experiment program in EBR-II	1981-94
	H. R. Thresh	Fabrication of fission product source	Ongoing
Quest Research	M. T. Lanagan	Microwave sintering of high-temperature superconducting wire	Ongoing
Reliance Electric	S. E. Dorris	Development of YBCO coils for superconductor motor	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Rhône-Poulenc	R. B. Poeppel, J. T. Dusek, U. Balachandran, M. T. Lanagan	Synthesis and properties of ceramic rare-earth superconductors	Ongoing
Ridge, Inc.	W. A. Ellingson	Microfocus radiography of ceramics	Ongoing
Rockwell International	K. Natesan	AFBC materials test	Ongoing
	H. H. Chung, C. A. Kot	Sodium-water reaction analysis and mitigation	Ongoing
	Y. W. Shin	Thermal-hydraulic analysis of SAFR	Ongoing
	L. A. Neimark	Fuel design for space reactor	1986-90
	F. A. Nichols, G. R. Fenske	Wear-resistant coatings	Ongoing
RPK Mechanics, Inc.	C. A. Kot	Validation of seismic calculation methods	Ongoing
Santa Fe Railroad	R. D. Carlson	Production of emergency response training film	1989
Seattle Specialty Chemicals	U. Balachandran	Processing of super- conductors	Ongoing
Shell Devel- opment (USA)	W. A. Ellingson	Nuclear magnetic resonance imaging of ceramics	Ongoing
	K. Natesan	Development of corrosion correlations	Ongoing
Siemens-KWU (Germany)	H. M. Chung	Irradiation-assisted stress corrosion	Ongoing
Siemens Medical Systems	W. A. Ellingson	Nuclear magnetic resonance imaging of ceramics	Ongoing
SKF-MRC Bearings	F. A. Nichols	Tribology; bearings; modeling	1989-90

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Sohio Engineered Materials	W. A. Ellingson	Nondestructive evaluation of structural ceramics	Ongoing
	J. P. Singh	Structural ceramics	Ongoing
Supercon Technologies	C. A. Youngdahl	Wires and junctions	Ongoing
Superconducting Products Co.	R. B. Poeppel	Conductor development	Ongoing
Superconductive Components	U. Balachandran	Processing of high-temperature superconductors	Ongoing
SuperconIX	K. C. Goretta	High-T _c single crystals	Ongoing
Taiwan Power Corp.	S. S. Chen	Flow-induced vibrations	1988-90
	W. T. Sha	Development of condenser computer code	Ongoing
Taylor Instruments	A. C. Raptis	Process instrumentation	Ongoing
Teledyne Cast Products	W. T. Sha, H. Domanus, R. Schmitt	Casting Modeling Consortium	1989-93
Teledyne Wahchang	H. M. Chung	Nodular corrosion of Zircaloy	Ongoing
TRW-Redondo Beach	K. Natesan	Materials tests for MHD slagging combustion	Ongoing
Toshiba (Japan)	H. M. Chung	Irradiation-assisted stress corrosion	Ongoing
	K. Natesan	Materials test/evaluation of fluidized bed combustion	Ongoing
United Technologies	T. M. Mulcahy, J. R. Hull	Superconductivity applications: magnetic bearings (cooperative program)	1988-90
	T. M. Kuzay	Si-SiC mirror bonding	Ongoing

<u>Organization</u>	<u>MCT Personnel</u>	<u>Subject of Collaboration</u>	<u>Duration of Collaboration</u>
Universal Energy Systems	F. A. Nichols, G. R. Fenske	Low-friction coatings for high-temperature applications	Ongoing
Vattenfalls Energie (Sweden)	H. M. Chung	Aging of cast steel in LWR	Ongoing
Vitreo-Retinal Consultants	T. M. Mulcahy	Comparison of intraocular magnets	Ongoing
Weirton Steel	N. Gopalsami	Sensors for the steel initiative	Ongoing
Westinghouse	L. A. Neimark et al.	Joint collaboration with PNC in EBR-II program	1981-94
	H. M. Chung	Field-ion atom probe analysis; irradiation-assisted stress corrosion cracking	Ongoing
	O. K. Chopra	Exchange of data and specimens on aging of cast stainless steel	Ongoing
	J. R. Hull, R. B. Poeppel	Current leads	Ongoing
Westinghouse Hanford	K. Natesan	ESD coatings for corrosion	Ongoing
Westinghouse Science and Technology Center	J. R. Hull, R. B. Poeppel, U. Balachandran, J. P. Singh, M. T. Lanagan, C. A. Youngdahl	Cryostat current leads	1989-90
W. J. Schafer and General Atomics	J. R. Hull	Superconducting magnetic energy storage	1990

1
 2
 3
 4
 5
 6
 7
 8
 9
 10
 11
 12
 13
 14
 15
 16
 17
 18
 19
 20
 21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42
 43
 44
 45
 46
 47
 48
 49
 50
 51
 52
 53
 54
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65
 66
 67
 68
 69
 70
 71
 72
 73
 74
 75
 76
 77
 78
 79
 80
 81
 82
 83
 84
 85
 86
 87
 88
 89
 90
 91
 92
 93
 94
 95
 96
 97
 98
 99
 100
 101
 102
 103
 104
 105
 106
 107
 108
 109
 110
 111
 112
 113
 114
 115
 116
 117
 118
 119
 120
 121
 122
 123
 124
 125
 126
 127
 128
 129
 130
 131
 132
 133
 134
 135
 136
 137
 138
 139
 140
 141
 142
 143
 144
 145
 146
 147
 148
 149
 150
 151
 152
 153
 154
 155
 156
 157
 158
 159
 160
 161
 162
 163
 164
 165
 166
 167
 168
 169
 170
 171
 172
 173
 174
 175
 176
 177
 178
 179
 180
 181
 182
 183
 184
 185
 186
 187
 188
 189
 190
 191
 192
 193
 194
 195
 196
 197
 198
 199
 200
 201
 202
 203
 204
 205
 206
 207
 208
 209
 210
 211
 212
 213
 214
 215
 216
 217
 218
 219
 220
 221
 222
 223
 224
 225
 226
 227
 228
 229
 230
 231
 232
 233
 234
 235
 236
 237
 238
 239
 240
 241
 242
 243
 244
 245
 246
 247
 248
 249
 250
 251
 252
 253
 254
 255
 256
 257
 258
 259
 260
 261
 262
 263
 264
 265
 266
 267
 268
 269
 270
 271
 272
 273
 274
 275
 276
 277
 278
 279
 280
 281
 282
 283
 284
 285
 286
 287
 288
 289
 290
 291
 292
 293
 294
 295
 296
 297
 298
 299
 300
 301
 302
 303
 304
 305
 306
 307
 308
 309
 310
 311
 312
 313
 314
 315
 316
 317
 318
 319
 320
 321
 322
 323
 324
 325
 326
 327
 328
 329
 330
 331
 332
 333
 334
 335
 336
 337
 338
 339
 340
 341
 342
 343
 344
 345
 346
 347
 348
 349
 350
 351
 352
 353
 354
 355
 356
 357
 358
 359
 360
 361
 362
 363
 364
 365
 366
 367
 368
 369
 370
 371
 372
 373
 374
 375
 376
 377
 378
 379
 380
 381
 382
 383
 384
 385
 386
 387
 388
 389
 390
 391
 392
 393
 394
 395
 396
 397
 398
 399
 400
 401
 402
 403
 404
 405
 406
 407
 408
 409
 410
 411
 412
 413
 414
 415
 416
 417
 418
 419
 420
 421
 422
 423
 424
 425
 426
 427
 428
 429
 430
 431
 432
 433
 434
 435
 436
 437
 438
 439
 440
 441
 442
 443
 444
 445
 446
 447
 448
 449
 450
 451
 452
 453
 454
 455
 456
 457
 458
 459
 460
 461
 462
 463
 464
 465
 466
 467
 468
 469
 470
 471
 472
 473
 474
 475
 476
 477
 478
 479
 480
 481
 482
 483
 484
 485
 486
 487
 488
 489
 490
 491
 492
 493
 494
 495
 496
 497
 498
 499
 500
 501
 502
 503
 504
 505
 506
 507
 508
 509
 510
 511
 512
 513
 514
 515
 516
 517
 518
 519
 520
 521
 522
 523
 524
 525
 526
 527
 528
 529
 530
 531
 532
 533
 534
 535
 536
 537
 538
 539
 540
 541
 542
 543
 544
 545
 546
 547
 548
 549
 550
 551
 552
 553
 554
 555
 556
 557
 558
 559
 560
 561
 562
 563
 564
 565
 566
 567
 568
 569
 570
 571
 572
 573
 574
 575
 576
 577
 578
 579
 580
 581
 582
 583
 584
 585
 586
 587
 588
 589
 590
 591
 592
 593
 594
 595
 596
 597
 598
 599
 600
 601
 602
 603
 604
 605
 606
 607
 608
 609
 610
 611
 612
 613
 614
 615
 616
 617
 618
 619
 620
 621
 622
 623
 624
 625
 626
 627
 628
 629
 630
 631
 632
 633
 634
 635
 636
 637
 638
 639
 640
 641
 642
 643
 644
 645
 646
 647
 648
 649
 650
 651
 652
 653
 654
 655
 656
 657
 658
 659
 660
 661
 662
 663
 664
 665
 666
 667
 668
 669
 670
 671
 672
 673
 674
 675
 676
 677
 678
 679
 680
 681
 682
 683
 684
 685
 686
 687
 688
 689
 690
 691
 692
 693
 694
 695
 696
 697
 698
 699
 700
 701
 702
 703
 704
 705
 706
 707
 708
 709
 710
 711
 712
 713
 714
 715
 716
 717
 718
 719
 720
 721
 722
 723
 724
 725
 726
 727
 728
 729
 730
 731
 732
 733
 734
 735
 736
 737
 738
 739
 740
 741
 742
 743
 744
 745
 746
 747
 748
 749
 750
 751
 752
 753
 754
 755
 756
 757
 758
 759
 760
 761
 762
 763
 764
 765
 766
 767
 768
 769
 770
 771
 772
 773
 774
 775
 776
 777
 778
 779
 780
 781
 782
 783
 784
 785
 786
 787
 788
 789
 790
 791
 792
 793
 794
 795
 796
 797
 798
 799
 800
 801
 802
 803
 804
 805
 806
 807
 808
 809
 810
 811
 812
 813
 814
 815
 816
 817
 818
 819
 820
 821
 822
 823
 824
 825
 826
 827
 828
 829
 830
 831
 832
 833
 834
 835
 836
 837
 838
 839
 840
 841
 842
 843
 844
 845
 846
 847
 848
 849
 850
 851
 852
 853
 854
 855
 856
 857
 858
 859
 860
 861
 862
 863
 864
 865
 866
 867
 868
 869
 870
 871
 872
 873
 874
 875
 876
 877
 878
 879
 880
 881
 882
 883
 884
 885
 886
 887
 888
 889
 890
 891
 892
 893
 894
 895
 896
 897
 898
 899
 900
 901
 902
 903
 904
 905
 906
 907
 908
 909
 910
 911
 912
 913
 914
 915
 916
 917
 918
 919
 920
 921
 922
 923
 924
 925
 926
 927
 928
 929
 930
 931
 932
 933
 934
 935
 936
 937
 938
 939
 940
 941
 942
 943
 944
 945
 946
 947
 948
 949
 950
 951
 952
 953
 954
 955
 956
 957
 958
 959
 960
 961
 962
 963
 964
 965
 966
 967
 968
 969
 970
 971
 972
 973
 974
 975
 976
 977
 978
 979
 980
 981
 982
 983
 984
 985
 986
 987
 988
 989
 990
 991
 992
 993
 994
 995
 996
 997
 998
 999
 1000
 1001
 1002
 1003
 1004
 1005
 1006
 1007
 1008
 1009
 1010
 1011
 1012
 1013
 1014
 1015
 1016
 1017
 1018
 1019
 1020
 1021
 1022
 1023
 1024
 1025
 1026
 1027
 1028
 1029
 1030
 1031
 1032
 1033
 1034
 1035
 1036
 1037
 1038
 1039
 1040
 1041
 1042
 1043
 1044
 1045
 1046
 1047
 1048
 1049
 1050
 1051
 1052
 1053
 1054
 1055
 1056
 1057
 1058
 1059
 1060
 1061
 1062
 1063
 1064
 1065
 1066
 1067
 1068
 1069
 1070
 1071
 1072
 1073
 1074
 1075
 1076
 1077
 1078
 1079
 1080
 1081
 1082
 1083
 1084
 1085
 1086
 1087
 1088
 1089
 1090
 1091
 1092
 1093
 1094
 1095
 1096
 1097
 1098
 1099
 1100
 1101
 1102
 1103
 1104
 1105
 1106
 1107
 1108
 1109
 1110
 1111
 1112
 1113
 1114
 1115
 1116
 1117
 1118
 1119
 1120
 1121
 1122
 1123
 1124
 1125
 1126
 1127
 1128
 1129
 1130
 1131
 1132
 1133
 1134
 1135
 1136
 1137
 1138
 1139
 1140
 1141
 1142
 1143
 1144
 1145
 1146
 1147
 1148
 1149
 1150
 1151
 1152
 1153
 1154
 1155
 1156
 1157
 1158
 1159
 1160
 1161
 1162
 1163
 1164
 1165
 1166
 1167
 1168
 1169
 1170
 1171
 1172
 1173
 1174
 1175
 1176
 1177
 1178
 1179
 1180
 1181
 1182
 1183
 1184
 1185
 1186
 1187
 1188
 1189
 1190
 1191
 1192
 1193
 1194
 1195
 1196
 1197
 1198
 1199
 1200
 1201
 1202
 1203
 1204
 1205
 1206
 1207
 1208
 1209
 1210
 1211
 1212
 1213
 1214
 1215
 1216
 1217
 1218
 1219
 1220
 1221
 1222
 1223
 1224
 1225
 1226
 1227
 1228
 1229
 1230
 1231
 1232
 1233
 1234
 1235
 1236
 1237
 1238
 1239
 1240
 1241
 1242
 1243
 1244
 1245
 1246
 1247
 1248
 1249
 1250
 1251
 1252
 1253
 1254
 1255
 1256
 1257
 1258
 1259
 1260
 1261
 1262
 1263
 1264
 1265
 1266
 1267
 1268
 1269
 1270
 1271
 1272
 1273
 1274
 1275
 1276
 1277
 1278
 1279
 1280
 1281
 1282
 1283
 1284
 1285
 1286
 1287
 1288
 1289
 1290
 1291
 1292
 1293
 1294
 1295
 1296
 1297
 1298
 1299
 1300
 1301
 1302
 1303
 1304
 1305
 1306
 1307
 1308
 1309
 1310
 1311
 1312
 1313
 1314
 1315
 1316
 1317
 1318
 1319
 1320
 1321
 1322
 1323
 1324
 1325
 1326
 1327
 1328
 1329
 1330
 1331
 1332
 1333
 1334
 1335
 1336
 1337
 1338
 1339
 1340
 1341
 1342
 1343
 1344
 1345
 1346
 1347
 1348
 1349
 1350
 1351
 1352
 1353
 1354
 1355
 1356
 1357
 1358
 1359
 1360
 1361
 1362
 1363
 1364
 1365
 1366
 1367
 1368
 1369
 1370
 1371
 1372
 1373
 1374
 1375
 1376
 1377
 1378
 1379
 1380
 1381
 1382
 1383
 1384
 1385
 1386
 1387
 1388
 1389
 1390
 1391
 1392
 1393
 1394
 1395
 1396
 1397
 1398
 1399
 1400
 1401
 1402
 1403
 1404
 1405
 1406
 1407
 1408
 1409
 1410
 1411
 1412
 1413
 1414
 1415
 1416
 1417
 1418
 1419
 1420
 1421
 1422
 1423
 1424
 1425
 1426
 1427
 1428
 1429
 1430
 1431
 1432
 1433
 1434
 1435
 1436
 1437
 1438
 1439
 1440
 1441
 1442
 1443
 1444
 1445
 1446
 1447
 1448
 1449
 1450
 1451
 1452
 1453
 1454
 1455
 1456
 1457
 1458
 1459
 1460
 1461
 1462
 1463
 1464
 1465
 1466
 1467
 1468
 1469
 1470
 1471
 1472
 1473
 1474
 1475
 1476
 1477
 1478
 1479
 1480
 1481
 1482
 1483
 1484
 1485
 1486
 1487
 1488
 1489
 1490
 1491
 1492

Appendix C: Honors, Awards, and Professional Activities

Honors and Awards

H. H. Chung

Winner of the ASME 1989 "Best 1988 Conference Session" award for organizing a technical symposium on *Seismic, Shock, and Vibration Isolation* held at the 1988 ASME Pressure Vessels and Piping Conference.

R. Lee and A. Mundy

Recipients of Honorable Mention Award for Crystals in Polarized Light photograph, published in *Industrial Photography*, Annual 1990 Specialized Scientific Imaging issue (June 1990).

K. Natesan

Recipient of paper award at 28th Symp. on *Engineering Aspect of Magnetohydrodynamics*, Chicago, IL (June 26-28, 1990); and best oral presentation award at 27th SEAM Symposium, Reno, NV (June 27-29, 1989).

J. Rest

Winner of Argonne National Laboratory Pacesetter Award for Development of the GRASS-SST/FASTGRASS Series of Fission Product Behavior Codes and for Excellence in Service to the U.S. Nuclear Regulatory Commission (April 1989).

J. P. Singh

Winner of Argonne National Laboratory Pacesetter Award for excellence in achievement and performance which truly surpasses normal job expectation (April 1990).

C. A. Youngdahl, J. Hull, R. Poeppel, M. Lanagan, J. Singh, U. Balachandran, B. Sayre, and R. Russell

Recipients of Certificate of Appreciation from Argonne National Laboratory for outstanding efforts in the fabrication of a first-of-a-kind high-temperature superconducting current lead for potential commercial application in cryogenic electric power equipment. This work was completed on a very demanding schedule and demonstrated Argonne's technical excellence and leadership position in high-temperature superconductor technology (April 1990).

Professional Society Activities

American Association of Physicists in Medicine

W. A. Ellingson, Member (1989 to present).

American Ceramic Society

U. Balachandran, Member, Electronics Division Program Committee (April 1989).

American Institute of Aeronautics and Astronautics

S. P. Vanka, Member, Propellants and Combustion Subcommittee (January 1985 to present).

American Society for Nondestructive Testing of Materials

W. A. Ellingson, Member (1985 to present).

American Society for Testing and Materials

J. Y. Park, Chairman, Subcommittee G1.08 on Corrosion of Nuclear Materials (November 1983 to February 1990).

J. Y. Park, Member, Committee E24 on Fracture Testing of Materials (1979 to present).

J. Y. Park, Member, Committee F04 on Medical and Surgical Materials (1981 to present).

American Society of Mechanical Engineers

S. S. Chen, Member, Technical Committee on Flow-Induced Noise and Vibration, Noise Control and Acoustics Division (1987 to present).

S. S. Chen, Fellow of the ASME (1987 to present).

S. S. Chen, Member, Pressure Vessel and Piping Committee, Nuclear Engineering Division (1987 to present).

S. S. Chen, Chairman, Technical Subcommittee on Fluid-Structure Interactions, Pressure Vessels and Piping Division (June 1987 to present).

S. S. Chen, Session Developer, Chairman, and Vice Chairman, ASME Pressure Vessels and Piping Conf., Honolulu, Hawaii, (July 23-27, 1989).

H. H. Chung, Member, Board on Nuclear Codes and Standards (June 1987 to present).

H. H. Chung, Member, Pressure Vessels and Piping Committee, Nuclear Engineering Division (June 1985 to present).

H. H. Chung, Member, Operations, Applications and Components Committee (1989 to present).

W. A. Ellingson, Fellow of the ASME.

W. A. Ellingson, Member (1985 to present)

B. J. Hsieh, Member, Technical Committee on Vibration and Sound Design Engineering Division (1989-1990).

J. R. Hull, Papers Review Chair, ASME Superconductivity Technical Committee in the Advanced Energy Systems Division (January 1988 to present).

J. R. Hull, Secretary, Member, Superconductivity Technical Committee on Advanced Energy Systems Division.

K. E. Kasza, Member, Committee on Fluid Transients (1987 to present).

C. A. Kot, Member, High Pressure Systems Committee, Subcommittee 6000 — Energy Release Protection (1984 to present).

D. Kupperman, 109th ASME Winter Ann. Mtg., Symp. on *New Directions in the NDE of Advanced Materials*, Argonne National Laboratory (May 1990).

T. M. Kuzay, Research Committee Member, Valley Chapter, Aurora Round House Regional Historic Landmark.

S. Majumdar, Member, Subgroup on Elevated Temperature Design, Boiler and Pressure Vessels Code Committee (May 1988 to present).

T. M. Mulcahy, Member, Special Working Group on Dynamic Analysis, Code Committee (1980 to present).

T. M. Mulcahy, Member, Technical Subcommittee on Fluid-Structure Interactions, Pressure Vessels and Piping Division (1987 to present).

Y. W. Shin, Member, Subcommittee on Fluid-Structure Interactions, Pressure Vessel and Piping Division (1986 to present).

M. G. Srinivasan, Member, Multiphase Flow committee (1988-1989).

P. Turula, Member, Subgroup on Containment Systems for Nuclear Spent Fuel and High-Level Waste Transport Packagings (1990-1995).

S. P. Vanka, Member, Fluid Mechanics Committee, Fluids Engineering Division; Polyphase Flow Committee, Fluids Engineering Division; and Propulsion Subcommittee, Aerospace Engineering Division (1983 to present).

M. W. Wambsganss, Member, Codes and Standards Committee, Subgroup on Vibration Monitoring of Internals, Task Group to Prepare Heat Exchanger Vibration Standard (1983 to present).

M. W. Wambsganss, Member, Technical Committee on Flow-induced Noise and Vibration, Noise Control and Acoustics Division (1983 to present).

ASM International, The Materials Information Society

K. Natesan, Member, Journal of Materials Engineering Committee (1990-1993).

Illinois Solar Energy Association

J. R. Hull, Member, Board of Directors (1988-1991).

Institute of Electrical and Electronics Engineers

A. C. Raptis, Member, IEDM-IEEE Detectors, Sensors and Displays Subcommittee.

Institute of Nuclear Materials Management

P. Turula, Member, INMM/ANSI-N14 Standards Committee for Packaging and Transportation of Radioactive Materials (1987 to present).

Joint Army, Navy, NASA, Air Force (JANNAF)

W. A. Ellingson, Member, Subcommittee on Nondestructive Evaluation.

National Association of Corrosion Engineers

K. Natesan, Vice Chairman, Committee on Materials for Fossil Fuels Combustion and Convection Systems (April 1989 to present).

Sigma Xi Honorary Society

W. A. Ellingson, Member (1978 to present).

TMS-AIME

P. S. Maiya, Member, Nuclear Metallurgy Committee (1986 to present).

K. Natesan, Member, Corrosion-Resistant Materials Committee (1982 to present).

Welding Research Council

S. S. Chen, Member, Task Force on Flow-Induced Vibration (1989 to present).

Other Committee Participation

U. Balachandran

Member, M.S. Thesis Committee, Dept. of Materials Engineering, San Jose State University (May 1989-April 1990).

M. C. Billone

Member, DOE/OFE International Thermonuclear Experimental Reactor Design Team.

M. C. Billone

Member, DOE/OFE Solid Breeder Working Group (October 1987 to present).

M. C. Billone

Chairman, Materials and Components Technology Division Library Committee (October 1987 to present).

M. C. Billone

Chairman, Materials and Components Technology Division Social Committee (January 1989 to present).

Y. S. Cha

Member, Materials and Components Technology Division Social Committee (January 1989 to present).

U. S. Choi

Member, International Energy Agency District Heating and Cooling Advanced Fluids Experts Group (1987 to present).

U. S. Choi

Member, M.S. Thesis Committee, School of Mechanical Engineering, Purdue University (March 1989 to present).

J. G. Daley

Vice-Chairman, Stirling Engine Committee of the ASME Advanced Energy Systems Division (August 1986 to present).

J. G. Daley

Member, Advanced Power Plant Committee of the Society of Automotive Engineers (1988 to present).

D. R. Diercks

Member, Review Panel, DOE Nuclear Engineering Research Grant Program (1988-1989).

S. E. Dorris

Member, Illinois Ceramics Advisory Group (February 1988 to present).

S. E. Dorris

Chairman, Building 212 Safety Committee (January 1989 to present).

S. E. Dorris

Member, Ph.D. Thesis Committee, Dept. of Materials Science and Engineering, Northwestern University (1988 to present).

W. A. Ellingson

Member, Thrust Group on Image Reconstruction and Processing, University of Chicago Center for Imaging Science (March 1988 to present).

W. A. Ellingson

Ph.D. Candidate Thesis Advisor and Member of Thesis Committee, Medical Physics Division, Dept. of Physiology and Biophysics, Chicago Medical School (April 1987 to August 1989).

W. A. Ellingson

Invited Lecturer and Host at four new test facilities, Argonne National Laboratory Conf. *Materials Evaluation and Inspection: New Methods, Materials and Dimensions*, Argonne, IL (September 25-26, 1989).

W. A. Ellingson

Member, Honorable Harris W. Fawell's Science and Technology Advisory Committee.

W. A. Ellingson

National Committee, DOE Fossil Energy National Task Force Leader for Coal Gasification Materials.

W. A. Ellingson

National Committee, Oak Ridge National Laboratory team for DOE funding areas.

W. A. Ellingson

Member, Materials and Components Technology Division Education Committee (1986 to present).

A. Erdemir

Member, Space and Naval Warfare Systems Command (SPAWAR) Evaluation Panel for IR&D Projects (March 1990 to present).

- K. C. Goretta
Member, M.S. Thesis Defense Committee, Illinois Institute of Technology (December 9, 1988).
- K. C. Goretta
Member, M.S. Thesis Committee, Metallurgical and Materials Engineering Department, Illinois Institute of Technology (April 1989 to present).
- K. C. Goretta
Member, Focus Group on DOE Scientific and Technical Information Needs, Argonne National Laboratory (June 1989).
- K. C. Goretta
Member, Materials and Components Technology Division Open House Planning Committee, Argonne National Laboratory (June-September 1989).
- B. J. Hsieh
Member, Materials and Components Technology Division Safety Committee (1986-1990).
- K. E. Kasza
Member, M.S. Thesis Committee, Dept. of Mechanical Engineering, Purdue University (1989).
- K. E. Kasza
Organizer and Chairman, International Energy Agency District Heating and Cooling Advanced Fluids Experts Group (May 1987 to present).
- K. E. Kasza
Member, ANL Multiphase Flow Research Institute Steering Committee (June 1985 to present).
- K. E. Kasza
ANL Program Coordinator for Fossil Energy Core Program, *Energy Transport Processes Mechanisms* (March 1987 to present).
- K. E. Kasza
ANL Program Coordinator for District Heating and Cooling (February 1986 to present).
- K. E. Kasza
Member, Ph.D. Thesis Committee, University of Illinois at Chicago (1989 to present).
- K. E. Kasza
Member, DOE National Technical Working Group on Heavy Water Reactor Thermal Hydraulics (1989 to present).
- K. E. Kasza
Member, DOE National Design Review Team for NPR-HWR: Thermal Hydraulics (1989).

C. A. Kot

Coordinator, NRC Steering Group on the Validation of Seismic Calculational Methods (1984 to present).

D. S. Kupperman

Member, Ph.D. Thesis Committee, Dept. of Mechanical Engineering and Applied Mechanics, Drexel University (January 1986 to present).

T. M. Kuzay

Workshop, DEP-Whiz Kid Program, The Verification of 3-D Close Form Solution of Heat Transfer Around a Superconducting Josephson Junction (June 1989).

T. M. Kuzay

Committee Member, Argonne Credit Union Search Committee for President (December 1989-May 1990).

T. M. Kuzay

Co-Chairman, Materials and Components Technology Division Conference Committee (1989-1990).

T. M. Kuzay

Committee Member, DOE, University Research Instrumentation (URI) program selection, Washington DC (July 1989).

W. H. Livernash

Member, Advanced Photon Source Safety Committee (May 1986 to present).

W. H. Livernash

Member, Plant Facilities and Services Advisory Committee (January 1988 to present).

W. H. Livernash

Member, SAR Review Committee for ATLAS Upgrade Project (September 1988 to present).

W. H. Livernash

Member, AMOS Customer Group (November 1988 to present).

W. H. Livernash

Member, Pressure Vessel Safety Committee (October 1988 to present).

W. H. Livernash

Member, Environmental Planning and Review Committee-NEPA Revision (March 1989 to present).

P. S. Maiya

Member, Nuclear Systems Materials Handbook Working Group MP-1 (1987 to present).

- P. S. Matya
Member, Intense Pulsed Neutron Source Enriched Target Safety Review (April 1988 to present).
- C. A. Malefyt
Member, ANL Copier Management Advisory Committee (1991).
- C. A. Malefyt
Volunteer Editor, Publications Committee, Society for Technical Communication (1990 to present).
- C. A. Malefyt
Representative, MCT Division Technology Transfer (1990 to present).
- G. A. McLennan
Member, Materials and Components Technology Division Library Committee (1988 to present).
- A. I. Michaels
Member, Government Steering Committee for the DOE-ECUT Sponsored ACTIS (A Computerized Tribological Information System) program (1987 to present).
- K. Natesan
Member, ORNL Review Team for Development of Sulfur-Resistant Protective Oxide Scales.
- K. Natesan
Member, ORNL Review Team on Materials Selection for Cross-Flow Filter Development.
- F. A. Nichols
Member, ASM Flow and Fracture Committee (1989 to present).
- F. A. Nichols
Member, ASM Atomic Transport Committee (1989 to present).
- R. B. Poeppel
Chairman, Materials and Components Technology Division Social Committee (1990).
- A. C. Raptis
Member, Review Board for the ANL/MUEC Multiphase Flow Research Institute.
- A. C. Raptis
Member, Review Panel for Nuclear Engineering Research (April 1989).
- A. C. Raptis
Member, DOE/NE Evaluation Team for Engineering Proposals submitted to Small Business Innovative Research Program.

A. C. Raptis

Member, Advisory Council for College of Engineering, University of Akron (1990).

J. Rest

Member, Materials and Components Technology Division Computer Committee (September 1986 to present).

J. Rest

Member, Advanced Photon Source Users Representatives from Argonne and the University of Chicago (March 1989 to present).

J. Rest

Member, Materials and Components Technology Division Promotion Committee (March 1990 to present).

M. G. Srinivasan

Member, Materials and Components Technology Division Ad Hoc Promotions Committee (1988–1990).

D. L. Telfer

Chairman, Materials and Components Technology Division Education Committee (May 1987 to December 1990).

D. L. Telfer

Chairman, Materials and Components Technology Division 300-Area Amenities Committee (May 1987 to December 1990).

D. L. Telfer

Member, Materials and Components Technology Division Automated Data Processing Committee (May 1987 to December 1990).

D. L. Telfer

Member, Argonne Combined Appeal Steering Committee (May 1988 to present).

D. L. Telfer

Member, Argonne Combined Appeal Fund-Raising Subcommittee (January 1988–February 1990).

D. L. Telfer

Chairman, Argonne Combined Appeal Fund-Raising Subcommittee (March 1990 to present).

D. L. Telfer

Member, Argonne Combined Appeal Training Subcommittee (January–December 1989).

D. L. Telfer

Member, Argonne Combined Appeal Publicity Subcommittee (March 1990 to present).

H. R. Thresh

Member, LILY Target Design Review Committee (February 1988 to present).

H. R. Thresh

Member, Intense Pulsed Neutron Source Booster Design Committee (April 1988 to present).

K. L. Uherka

Chairman, Materials and Components Technology Division 300-Area Safety Committee (August 1986 to present).

K. L. Uherka

Ad Hoc Member, Materials and Components Technology Division Computer Committee (October 1986 to present).

K. L. Uherka

Member, Joint ANL/NASA-LeRC Task Force on Aerospace Applications of High-Temperature Superconductivity (1988 to present).

K. L. Uherka

Member, DOE/CH Technical Review Board for Reviewing Industrial Heat Pump proposals.

K. L. Uherka

Member, DOE/HQ Technical Evaluation Committee for Reviewing Small Business Research Initiative proposals.

M. W. Wambsganss

Associate Member, Shellside Flow and Vibration Subcommittee, Heat Transfer Research, Inc., Alhambra, CA (1988 to present).

M. W. Wambsganss

Member, Committee on Heat Transfer and Heat Exchangers, International Energy Agency, Program of Energy Conservation (1978 to present).

C. K. Youngdahl

Member, Materials and Components Technology Division Social Committee (1989-1990).

C. K. Youngdahl

Member, Membership Committee, Sigma XI, ANL Chapter (January 1990 to present).

Invited Teaching and Research at Other Institutions

U. Balachandran

Lecturer, 2nd Summer School on New Materials, University of Sao Paulo, San Carlos, Brazil (February 20-March 3, 1990).

S. S. Chen

Lecturer, Short Course on *Flow-Induced Vibration*, Taiwan Power Co., Taipei, Taiwan (May 22-30, 1989).

H. M. Chung

Invited Member, Intl. Atomic Energy Agency Field Expert, Nuclear Fuel Cycle Technology-Zircaloy Performance and Characterization, Korea Atomic Energy Research Institute (Oct. 28-Nov. 28, 1989).

H. M. Chung

Invited Expert, LWR Advanced Fuel Development, Institute of Nuclear Energy Research, Taiwan (Nov. 14-18, 1989).

W. A. Ellingson

Adjunct Professor, Medical Physics, Chicago Medical School (April 1987 to present).

N. Gopalsami

Joint Research, Applied Physics Dept., U. S. Army Tank-Automotive Command, Warren MI, (June 1987 to present).

J. R. Hull

Member, Research Advisory Board, Texas Solar Pond Consortium (March 1989 to present).

J. R. Hull

Invited Member, Texas Solar Pond Consortium, Research Advisory Board.

J. Y. Park

Adjunct Professor, Dept. of Civil Engineering, Mechanics & Metallurgy, University of Illinois at Chicago (December 1988 to present).

Invited Conference Participation

U. Balachandran

1st Intl. *Ceramic Science and Technology* Congress of the American Ceramic Society, Anaheim, CA, October 31-November 3, 1989: Invited Technical Session Chairman.

U. Balachandran

1st Intl. *Ceramic Science and Technology* Congress of the American Ceramic Society, Anaheim, CA, October 31-November 3, 1989: Session Chairman.

U. Balachandran

Symp. on *Ceramic Superconductors*, The 2nd Intl. Ceramic Science and Technology Congress, Orlando, FL, November 13, 1990: Program Chairman.

S. S. Chen

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, Session on *Flow-induced Vibration*: Organizer and Vice-Chairman.

S. S. Chen

Program Committee, International Conf. *Engineering on Aero-Hydroelasticity*, Prague, Czechoslovakia, December 5-8, 1989: Member.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, Session on *Dynamics of Plates and Shells (II)*: Organizer and Vice-Chairman.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, Session on *Dynamics of Plates and Shells (III)*: Coorganizer.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989: Coorganizer, Session on *Dynamics of Plates and Shells (IV)*.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, 3rd Symp. on *Seismic, Shock, and Vibration Isolation (I)*: Organizer and Chairman.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, Session on *Fracture Mechanics and Plasticity*: Vice-Chairman.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, 3rd Symp. on *Seismic, Shock, and Vibration Isolation (III)*: Organizer.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, Symp. on *Seismic, Shock, and Vibration Isolation (V): Application to Buildings and Industrial Facilities*: Coorganizer.

H. H. Chung

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989, 3rd Symp. on *Seismic, Shock, and Vibration Isolation (VI): Panel Session-1: State-of-the-Art in Isolation System Design*: Organizer and Vice-Chairman.

H. M. Chung

Ninth Intl. Conf. on *Zirconium in the Nuclear Industry*, Kobe, Japan, November 5-8, 1990: Member, Session Organization and Paper Selection Committee.

W. A. Ellingson

Symp. on *Advanced Tomographic Imaging Methods for the Study of Materials*, Fall 1990 MRS Mtg., Boston, MA, November 26-December 1, 1990: Organizer.

W. A. Ellingson

92nd Ann. Mtg. of Am. Ceram. Soc., Dallas, TX, April 22-26, 1990: Session Chairman.

W. A. Ellingson

Fossil Energy Materials, Oak Ridge, TN, May 15-17, 1990: Session Chairman.

W. A. Ellingson

Conference on *Evaluation of Modern Ceramics*, Cosponsored by American Ceramic Society and American Society for Nondestructive Evaluation, July 9-12, 1990, Columbus, OH: Program Cochairman.

J. R. Hull

Am. Solar Energy Soc. Conf., *Photovoltaic System Modeling*, June 1989: Member, Session Committee.

J. R. Hull

Magnetic Bearing Symp., Intersoc. Energy Conv. Engineering Conf., Reno, NV, August 1990: Organizer.

D. Kupperman

Workshop on *Application of Neutron Diffraction to the Determination of Residual Stresses in Engineering Materials*, Argonne National Laboratory, May 1990: Coorganizer.

T. M. Kuzay

An Overview of the *Engineering Solutions to High Heat Load Optics*, 1990 SPIE Int. Mtg., San Diego, July 8-13, 1990: Invited speaker.

K. V. Liu

Mid-America Chinese Professional Annual Conv., Chicago, IL June 2-4, 1989: Convention Cochairman.

Mulcahy, T. M.

Division J, *Structural Dynamics of Extreme Load Analysis*, SMIRT-11, Tokyo, Japan, August 1990: Coordinator.

R. B. Poeppel

HTSC Processing Workshop, Argonne National Laboratory, June 12, 1990: Session Chairman.

R. B. Poeppel

Superconductivity: The Manufacturing Challenges, Chicago, IL, Oct 16-18, 1990: Member, Conference Advisory Committee.

R. B. Poeppel

First International *Ceramic Science and Technology* Congress of the American Ceramic Society, Anaheim, CA, Oct 31-Nov. 3, 1989: Session Chairman.

R. B. Poeppel

High-Temperature Superconductors, Satellite Symp. 4 of the 7th CIMTEC World Ceramics Congress, Montecatini Terme, Trieste, Italy, July 2-5, 1990: Member, International Advisory Committee.

J. Rest

Society of Research Administrators 1989 Southern Section Meeting, San Juan, Puerto Rico, May 2-5, 1989: Speaker.

J. Rest

New England *Technology Transfer* Conference, Boston, MA, April 3-4, 1990: Speaker and Panel Participant.

Y. W. Shin

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989: Symp. on *Transient Thermal-Hydraulics in Vessel and Piping Systems-I*: Organizer and Chairman.

Y. W. Shin

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989: Symp. on *Transient Thermal-Hydraulics in Vessel and Piping Systems-II*: Organizer and Vice-Chairman.

Y. W. Shin

1989 ASME PVP Conf., Honolulu, HI, July 23-27, 1989: Symp. on *Transient Thermal-Hydraulics in Vessel and Piping Systems-III*: Organizer and Chairman.

Y. W. Shin

1990 ASME PVP Conf., Nashville, TN, June 17-21, 1990: *Transient Thermal Hydraulics and Resulting Loads on Vessel and Piping Systems-I*: Session Developer.

Y. W. Shin

1990 ASME PVP Conf., Nashville, TN, June 17-21, 1990: *Transient Thermal Hydraulics and Resulting Loads on Vessel and Piping Systems-II*: Session Developer and Chairman.

Y. W. Shin

1990 ASME PVP Conf., Nashville, TN, June 17-21, 1990: Symp. on *Transient Thermal-Hydraulics and Resulting Loads on Vessel and Piping Systems*: Developer and Organizer.

Y. W. Shin

U.S. Efforts on Analytical Models/Codes for Large Leaks, U.S./European Steam Generator Specialists' Meeting, San Jose, CA, March 26-28, 1990: Speaker.

K. L. Uherka

DOE/OIP Workshop and Program Review *Industrial Magnetic Heat Pump*, San Francisco, CA, December 12-13, 1989: Speaker and Participant.

H. Wiedersich

Program Committee for Fourth Intl. Conf. on *Fusion Reactor Materials*, Kyoto, Japan (December 4-8, 1988): Member.

C. A. Youngdahl

Discussion panel on *Criteria for Critical Current Measurements of High-T_c Superconductors*, U.S. Dept. of Energy, Washington, DC (April 10, 1989): Invited Member.

Editorial Activities

M. K. Au-Yang, S. S. Chen, S. Kaneko, and R. Chilukuri

Editors, Proc. 1989 ASME Pressure Vessels and Piping Conf. Honolulu, Hawaii, June 23-27, 1989, The American Society of Mechanical Engineers, New York (1989), PVP-Vol. 154.

S. S. Chen

Member of the International Advisory Editorial Board, Pergamon Press and Huazhong University of Science and Technology.

J. R. Hull

Associate Editor, *Solar Ponds (Solar Energy)* (September 1986 to present).

D. S. Kupperman

Associate Technical Editor, *Materials Evaluation (ASNT Journal)* (1986 to present).

K. V. Liu

Reviewer: *Journal of Heat Transfer*, Transactions of American Society of Mechanical Engineers (1989-1990).

D. C. Ma, J. Tani, S. S. Chen, and W. K. Liu

Editors, Proc. 1989 ASME Pressure Vessels and Piping Conf. Honolulu, Hawaii, June 23-27, 1989, The American Society of Mechanical Engineers, New York (1989), PVP-Vol. 157.

F. J. Moody (G. E. Nuclear Energy), Y. W. Shin, and J. Colton (SRI Intl.)

Editors, Proceedings 1990 Pressure Vessels and Piping Conference, Nashville, TN, June 17-21, 1990, The American Society of Mechanical Engineers, New York (1990), PVP Vol. 190.

K. L. Uherka

Reviewer, *Journal of Applied Physics and Applied Physics Letters (Superconductor Application)* (September 1988 to present).

Appendix D: Other MCT Publications

This appendix is a list of publications produced by the MCT personnel who were transferred to the new Reactor Engineering Division in October 1990. The list reflects their publications through September 30, 1990.

Performance of a Multi-Grid Three-Dimensional MHD Generator Calculation Procedure

J. X. Bouillard (ES), J. L. Krazinski, S. P. Vanka, and G. F. Berry (ES)

Proc. 27th Symp. on *Engineering Aspects of Magnetohydrodynamics*, Reno, NV, June 27-29, 1989, ed. J. Martin Bauer, The American Society of Mechanical Engineers, New York (1990), pp. 5.2-1-5.2-11.

User's Manual for MGMHD: A Multigrid Three-Dimensional Computer Code for the Analysis of Magnetohydrodynamic Generators and Diffusers

J. X. Bouillard (ES), J. L. Krazinski, S. P. Vanka, and G. F. Berry (ES)

ANL/MHD-89/1 (1989).

The Onset of Boiling of the Liquid Alkali Metals

R. E. Holtz and P. A. Lottes (RAS)

To be presented at the 7th Symp. on *Space Nuclear Power Systems*, Albuquerque, NM, January 7-11, 1990.

Impact of High-Critical-Temperature Superconductors on Electromagnetic Pump Application

J. L. Krazinski, R. E. Holtz, and R. A. Jaross

ANL/MCT-90/1 (May 1990).

A Computational Fluid Dynamics and Chemistry Model for Jet Fuel Thermal Stability

J. L. Krazinski, S. P. Vanka (University of Illinois at Urbana-Champaign), J. A. Pearce (WRDC/Aero Propulsion and Power Laboratory), and W. M. Roquemore (WRDC/Aero)

Proc. 35th ASME *Intl. Gas Turbine and Aeroengine Congress and Exposition* Centre, Brussels, Belgium, June 11-14, 1990, to be published in Trans. ASME, Preprint 90-GT-33, pp. 1-7.

Examination of Ledinegg Flow Stability Criteria for Liquid Metal Systems

P. A. Lottes (RAS) and R. E. Holtz

To be presented at the 7th Symp. on *Space Nuclear Power Systems*, Albuquerque, NM, January 7-11, 1990.

Analysis of Pressure Drop and Heat Transfer Data from the Reversing Flow Test Facility

Paul D. Roach and Kenneth J. Bell (Oklahoma State University)

ANL/MCT-88-2 (May 1989).

Fouling in Jet Fuels: A New Approach

W. M. Roquemore (WRDC/Aero Propulsion and Power Laboratory), J. A. Pearce (WRDC/Aero), W. E. Harrison III (WRDC/Aero), J. L. Krazinski, and S. P. Vanka
Proc. Symp. on *The Structure of Future Jet Fuels II*, Miami Beach, FL, September 10-15, 1989, American Chemical Society, Washington, DC, 1989, pp. 841-849.

Aeronautical Applications of High-Temperature Superconductors

G. E. Turney (Lewis Research Center), R. W. Luidens (Lewis Res. Ctr.), K. Uherka, and J. Hull

Prepared for Aircraft Design, Systems and Operations Conf., Seattle, WA, July 31-August 2, 1989, NASA Technical Memorandum 102311.

Recent Advances in Magnetic Heat Pump Technology

K. L. Uherka, J. R. Hull, and P. E. Scheihing (DOE)

Presented at ASME 1989 Winter Annual Mtg., San Francisco, CA, Dec. 10-15, 1989. Published in *Advances in Industrial Heat Pumps Technology-1989*.

An Efficient Computational Tool for Ramjet Combustor Research

S. P. Vanka, J. L. Krazinski, and A. S. Nejad (AFWAL/POPT, Wright Patterson Air Force Base)

Jet Propulsion Power 5(4), 431-437 (August 1989).

Evaluation of Industrial Magnetic Heat Pump/Refrigerator Concepts that Utilize Superconducting Magnets

J. A. Waynert (Astronautics Corporation of America), A. J. DeGregoria (ACA), R. W. Foster (ACA), J. A. Barclay (ACA), and K. L. Uherka

ANL-89/23 (June 1989).

Program Index

Acoustic Leak Detection and Location: 136

Advanced Energy Transmission Fluids: 120

Advanced Neutron Source: 2, 63, 68

Advanced Photon Source: 120

Arms Control: 128, 129

Basic Energy Sciences, DOE: 117

Casting Modeling: 107

COMMLX Code: 104–107

Conservation and Renewable Energy, DOE: 1, 117, 131–133

Defense, DOE: 1

District Heating and Cooling: 119

Environment, Safety and Health, DOE: 1

Flow-Induced Vibrations: 116

Fossil Energy, DOE: 1, 5, 40, 109–110, 130, 131

Fusion Energy, DOE: 1, 41–42

Heavy Water Reactors: 39

Integral Fast Reactor: 1, 6, 10, 56, 62, 66, 90

International Thermonuclear Experimental Reactor: 41, 56, 63

Ion-Beam-Assisted Deposition: 76–78

Light-Water Reactors: 1, 10, 36–39, 57–61

Magnetic Bearings: 100

Magnetic Levitation (Maglev) Systems: 101, 121

Multiphase Flow and Heat Transfer: 117

National Park Service: 1

National Science Foundation: 1

National Tribology Program: 3

New Production Reactors: 1, 39, 56, 119

Nuclear Energy, DOE: 1

Nuclear Regulatory Commission: 1, 2, 36, 56, 60, 122, 146

Nuclear Waste Storage: 59

Reduced-Enrichment Fuels: 56, 66

Safety Analysis Reports for Packaging (SARPs): 146–154

Sodium Heat Engine: 64, 133

Solid Oxide Fuel Cell: 65

Superconducting Magnetic Energy Storage: 101

Transportation, U.S. Department of: 2, 146

Transportation Materials, DOE: 79

Transportation Technologies, DOE: 76

Transportation Management, DOE: 1, 155

Tribological Testing: 79

Tritium Inventory and Release Analysis (TIARA) code: 64

Ultrasonic Imaging and NDE: 130–131

VICTORIA Code: 62

Waste Operations, DOE: 155

END

**DATE
FILMED**

3 / 10 / 93