62/3-10-93 ST Q

PREPARED FOR THE U.S. DEPARTMENT OF ENERGY,
UNDER CONTRACT DE-AC02-76-CHO-3073

PPPL-2867
UC-420,421,423,426

PPPL-2867

REDUCED OPTICAL TRANSMISSION OF SiO_2 FIBERS
USED IN CONTROLLED FUSION DIAGNOSTICS

BY

A.T. RAMSEY, H.G. ADLER, AND K.W. HILL

FEBRUARY, 1993

PPPL

PRINCETON
PLASMA PHYSICS
LABORATORY

NOTICE

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial produce, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

NOTICE

This report has been reproduced from the best available copy.
Available in paper copy and microfiche.

Number of pages in this report: 13

DOE and DOE contractors can obtain copies of this report from:

Office of Scientific and Technical Information
P.O. Box 62
Oak Ridge, TN 37831;
(615) 576-8401.

This report is publicly available from the:

National Technical Information Service
Department of Commerce
5285 Port Royal Road
Springfield, Virginia 22161
(703) 487-4650

Reduced Optical Transmission of SiO₂ Fibers Used In Controlled Fusion Diagnostics

A. T. RAMSEY, H. G. ADLER, and K. W. HILL

Princeton Plasma Physics Laboratory,
Princeton University
PO Box 451
Princeton, New Jersey 08543

We have subjected a silica core fiber optic cable to 4 years of low-level neutron and gamma radiation from Princeton's TFTR controlled fusion experiment. The accumulated dose was 200 Gy. As a result of the radiation, we have measured increased attenuations of 100 - 300 dB/km in the visible part of the spectrum, and a decrease of the numerical aperture. An attempt to decrease this damage by photobleaching failed. We argue that this failure is not unexpected, since the rate of damage is so slow and the time scale so long that the self-annealing process keeps the residual damage at the irreducible level seen in other experiments. The implications of these findings for controlled fusion diagnostics during upcoming experiments with highly reactive deuterium-tritium plasmas are discussed.

1 Introduction

The use of high purity fused silica optical fibers to transmit visible light from controlled fusion experimental chambers to a remote data handling area has grown enormously in the past 10 years. Now there is virtually no experiment without a set of optical fibers. At the same time, the progress of the field has meant that radiation from fusion products is creating radiation fields high enough that their effects cannot be ignored. In particular, the current large tokamaks (JET, JT-60, TFTR, and DIII-D) have achieved levels of temperature and confinement which result in substantial amounts of deuterium fusion. Princeton's TFTR will soon move to the much more reactive mixture of deuterium and tritium (D - T). Shortly after, JET, the European Community's tokamak, will begin its final campaign using a D - T plasma. We can expect the D - T fusion rate, and the accompanying radiation, to increase about 200 times above the present D - D levels.

The radiation effects in fibers arise primarily from (n, γ) reactions in the material in the vicinity of the tokamak. The neutrons, emitted in the reaction $D + D \rightarrow He^3 (0.8 \text{ MeV}) + n (2.45 \text{ MeV})$, are quickly thermalized and captured. The resulting nuclei are almost always in an excited state, and relax with the emission of gamma rays with energies ranging from several MeV down into the keV range. In the D - T phase, the reaction is $D + T \rightarrow \alpha (3.5 \text{ MeV}) + n (14 \text{ MeV})$. The gamma rays cause two serious problems in an optical fiber. They cause fluorescence in the fiber (either directly or from Compton- or photo-electrons), which adds a spectrally broad background under the desired signal. They also cause damage to the structure of the fiber which reduces the signal and changes the calibration of the system. (Diagnostic fibers usually carry analog signals.) Both of these radiation effects vary in time, and will be difficult to separate from the desired signals.

In an earlier paper, we reported the first measurements of radiation induced fiber

MASTER

ef

fluorescence in a tokamak diagnostic.¹ We also showed evidence for radiation induced opacity (and for its self annealing) during a plasma discharge, and mentioned that the fibers showed signs of permanently damaged transmission. Similar measurements have been reported by Morgan on his fiber system at JET, although he has not seen evidence of the self annealing which we have reported.²

In this paper we report the results of transmission measurements on a fiber exposed to long term, relatively low level, radiation from TFTR, and compare it to a sample from the same spool which has not been exposed to radiation. This is the first study of these effects arising from the radiation field produced by the current generation of controlled fusion experiments. The effects are large, with an added attenuation of 0.3 dB/m resulting from radiation damage accumulated over 4 years of low yield fusion experiments. (Undamaged fibers typically have attenuations of 0.03 dB/m at these wavelengths.) We also have measured the numerical aperture (NA) of the fibers, and find a marked decrease in the NA of the irradiated fiber. Finally, we report on our unsuccessful attempts to photo-bleach the radiation damage using a He - Ne laser.

2 Transmission Measurements

Absolute transmission measurements are much more difficult than relative ones. We have taken the easier route of comparing the transmission of a fiber exposed to radiation in the TFTR test cell with the transmission of two other lengths of fiber from the same batch but not exposed to radiation. All three fibers we cut from one length of QSF600A, a 600 μm core, polymer clad, high purity fused silica fiber manufactured by Quartz & Silice (now Fibres Optiques Industries). We purchased a 608 m length in 1988 (manufacturer's lot number GP20527). The transmission at 0.85 μm was measured as 6.04 dB/km by the manufacturer. (The nominal attenuation is about 4 dB/km for this fiber type.) The fiber that was exposed to radiation was a loop 103.6 m long. We ran it from our data acquisition area in the basement of the TFTR building up to the Test Cell (which contains the tokamak) and back again. We installed the loop in July, 1988, cutting it from near the beginning of the spool. Later, we cut fibers of 36.3 m and 1.6 m from near the end of the spool. All three fibers were terminated at both ends by Radiall crimp-on ferrules, type F 706054000. On our 40-channel fiber optic system HAIFA (H-Alpha Interference Filter Array), we use a fiber cleaver to prepare the ends of fibers.³ The minor losses and non-uniformities that this termination introduces are unimportant for that system. For the present transmission and N.A. tests, we needed a more uniform technique, so we polished all the ends, finishing with a 0.3 μm aluminum oxide lap. We inspected the ends visually; all 6 fiber ends appeared identical.

Figure 1 shows the experimental configuration of the test cell loop for the measurements. Off-the-shelf instrument indicator LEDs were mounted in a female bulkhead ferrule connector. The ferrule at one end of a fiber was screwed into the connector so that the fiber end was in contact with the top center of the LEDs plastic case. The other end of the fiber was inserted into a 10 cm diameter integrating sphere. A photodiode detector (EG&G HUV 1000B, operated in the zero-bias mode) looked into the side of the sphere at a location where it was not illuminated by the optical exit cone of the fiber.

The measured LED signal intensities were low when coupled this way, and because some authors (cited below) have reported photobleaching at very low power densities we made no

Figure 1-The radiation in the Test Cell which is causing the damage and the fluorescence is primarily a gamma ray flux resulting from the (n,g) reactions of the thermalized neutrons. This radiation is largely isotropic, but is stronger close to the machine: that is both where the neutrons are produced and where most of the neutron capture sites are located. The floor is 2 m thick under the machine, and is boron-bearing concrete. We assume that all the damage is done to that section of the fiber which is above the floor, about 7 m. The LEDs were used for the transmission tests. They were replaced by a beam-expanded laser for the numerical aperture tests.

Figure 2-Here are the spectral characteristics of three light emitting diodes used to measure the transient and static transmission of the fibers. These diodes are common green, yellow, and red instrument panel lights from our stockroom. We run them with current levels below saturation, typically about 10 mA. LED's can be modulated to a good square wave, which makes data analysis easy. Their spectral widths allow resolution of the wavelength dependence of the transmission. The positions of two critical wavelengths, visible bremsstrahlung and H_α , are shown on the graph.

effort to increase the levels. Instead, we used a lock-in detector to detect signals which were well buried in the detector's broad band noise (0 - 1 kHz). The LEDs were driven by a voltage and frequency stabilized 50 Hz square wave. The LED driving voltage was used by the lock-in as a reference.

We used three LEDs, covering the most widely used band of wavelengths used by fiber-based diagnostics. Our most sensitive wavelength in TFTR fiber diagnostics is 523 nm, where a line-free region offers a chance to measure the weak continuum radiation of electron bremsstrahlung. This signal is a measure of plasma purity, and is a major diagnostic tool.^{4, 3} For that reason, the green LED transmission tests are most important. We also have used a yellow and a red LED. The red offers a good measure of behavior in the important region of H_α radiation at 656 nm (the hydrogen $n = 3 \rightarrow n = 2$ transition).

The spectra of the LEDs is shown in Figure 2. Although there is overlap in the LED output spectra, the resolution is adequate for measuring broadband radiation induced transmission loss.

The signal at the detector in Fig. 1 depends on source brightness and input and output coupling as well as the fiber transmission. To eliminate this uncertainty, we compared the ratio of the light transmitted by the fiber shown in Fig. 1 with that transmitted by the undamaged fibers, using the same source and detector arrangement. With this technique, only the bulk transmission enters, since we have taken pains to make the other effects the same. We expect the transmission to fall as

$$1) \quad T \propto e^{-kL},$$

where L is the length of the fiber and k is the attenuation coefficient in m^{-1} .

Figure 3 - The detector signal for the three LEDs in each of the three fibers. Since the attenuation of the fibers is exponential in length, the deviation of the Test Cell fiber point from the line drawn through the reference fibers on this semi-log graph shows additional attenuation in that fiber arising from radiation damage.

Figure 4 - The transmission data for the damaged and undamaged fibers (the fiber that runs to the Test Cell and back and the fibers that have stayed spooled in storage). The horizontal error bars are the full-width at half-maximum of the LED spectra used to measure the transmission (see Fig. 2), and the vertical error bars are an estimate of the uncertainty in the transmission measurement. The curve is the manufacturer's typical transmission data for this type of fiber. The data from the damaged fiber suggest that the effect of radiation on transmission increases at shorter wavelengths.

probably is little damaged. Although the shielding factor is complicated by penetrations for diagnostic and operational access to the tokamak, the attenuation by the floor of both neutrons and gamma rays is expected to be a factor of more than 100.⁶ In this case, the transmission of the fiber can be broken into two parts,

In Figure 3, we show the raw signals of the three LEDs for the three fibers on a log axis, plotted as a function of the total fiber length. Since the signal should fall exponentially with length, the fact that the data from the Test Cell loop do not lie on the straight line of the two unexposed fibers shows that the Test Cell loop is damaged.

Figure 4 shows the fiber attenuation as a function of wavelength for the undamaged and damaged fibers. The slope of the first two points in Fig. 3 determines the value of k in Eq. 1) for the undamaged fiber. We have calculated

$$2) \quad k = \frac{\ln \left(\frac{S_{\text{long}}}{S_{\text{short}}} \right)}{L_{\text{long}} - L_{\text{short}}}$$

for each of the three colors, and for the damaged and undamaged fibers. S is the detector signal for the fibers, and L is the length. In Fig. 4, we have plotted the attenuations in dB/km, the usual units, on a graph which also shows the typical transmission of this fiber from data supplied by the manufacturer. The data for the undamaged fiber are in good agreement with the manufacturer's specifications. The data for the damaged fiber show a larger increase in attenuation at shorter wavelengths, an effect which has been seen before in studies done at much higher levels of radiation.⁵

The data in Fig. 4 are incomplete, however, in the sense that the damaged section in the Test Cell fiber is probably limited to the length of fiber above the floor in the Test Cell. This section is only 7 m long. The floor under the tokamak is a good shield for both neutrons and gamma rays, and the section in the Test Cell basement

3)

$$T = T_{\text{basement}} \times T_{\text{Test Cell}} \propto e^{-k_b L_b} \times e^{-k_{TC} L_{TC}}$$

and we shall assume that the attenuation in the basement, k_b , is the same as the undamaged fiber attenuation. What we have really plotted above in Fig. 4 for the damaged fiber is an effective attenuation, k_{eff} . If we express the attenuation in the damaged section as the sum of the normal attenuation and an added part due to radiation, $k_{TC} = k + \Delta$, we find that the effective attenuation we have shown above in Fig. 4 can be expressed as

$$4) \quad k_{\text{eff}} = k + \frac{L_{TC}}{L_{TC} + L_b} \Delta$$

This added attenuation, Δ , is 300 ± 50 dB/km in the green, and 140 ± 50 dB/km in the red. These values are much larger than the undamaged levels.

We now need to ask what exposure caused such a loss in transmission. The Test Cell loop fiber was installed in July, 1988. Since that time, TFTR has made about 30,000 high-current plasma discharges, for a total plasma duration of about 50 hours. Hot fusing plasmas, produced by auxiliary heating, occurred during only a small fraction of the total plasma time. We have had perhaps 3 hours of plasmas which produce substantial radiation from the reaction $D + D \rightarrow He^3 + n$ and the subsequent (n, γ) reactions following capture of the neutron. Between August 1988 and September 1992, when we took the transmission data shown above, TFTR produced 5.3×10^{19} neutrons. Measurements and modeling of the radiation produced by neutrons in the TFTR Test Cell predict that 1×10^{19} D - D neutrons produce 40 Gy (1 Gy = 100 Rad) at the location of the fiber loop.⁶ From this, we estimate that the Test Cell fiber has accumulated 200 Gy, with an error perhaps as large as a factor of 2. This large error arises because the radiation field varies strongly with distance just at the edge of the tokamak, and the TC loop is not in a well defined position, but comes up through the floor and winds around the vacuum vessel, then returns.

Figure 5—The integrated neutron production on TFTR for the 4 years from the time of installation of the Test Cell fiber loop to the conclusion of the run of 1992. Neutron production is shown versus calendar day. During times when the machine was undergoing upgrades there was no neutron production; these are the long flat periods.

Figure 5 shows the integrated neutron production by TFTR plotted as a function of calendar day during the 2 years that the fiber loop was in the Test Cell. This is a low rate of radiation and subsequent damage. A typical high reactivity shot produces perhaps 2×10^{16} n/s for 0.5 sec, yielding a radiation dose of 0.08 Gy to the fiber. Figure 5 is made up of a staircase of such small increases over 4 years.

To put our observations into perspective, we must look at the other work on this field. The subject of radiation damage to fibers is of importance to a number of people. Fiber communication links are widely used by both the nuclear fission power community and the nuclear weapons labs. A great deal of work

has been done in support of these needs. An excellent summary has been given by Friebele *et al.*⁷ A common link through this work is a large variation in susceptibility to radiation. Small differences in fiber composition or manufacturing techniques result in large (greater than an order of magnitude) differences in attenuation for the same dose rate. That said, our results are consistent with other measurements in many respects, and we may make the following observations.

At the low dose rate and over the extended period of damage, we expect the transient effects to be gone. The complex self-annealing behavior of the radiation damage in all fibers tested is complete in about 10^5 s; our measurements were made more than 10^7 s after most of the radiation. Therefore, we are looking at the equilibrium state of the transmission. Data shown by Friebele show that the equilibrium attenuation levels are typically 5% of the level immediately after damage. Current thinking is that attenuation is due primarily to the formation of alkali-electron centers (even at the alkali levels of only 40 - 90 ppb typical of high purity fused silica cores). Both the self-annealing and the photobleaching can be well modeled by this assumption. We know of no similarly accurate description of the residual attenuation, but one readily can believe that some of the defects are so strongly pinned that bimolecular recombination (the supposed annealing mechanism) is totally inhibited. (We shall discuss another possible source of the irreducible attenuation in the next section.) Since most fiber communication work is done in the infrared, it is not surprising that studies have concentrated almost exclusively on transmission at 0.82 μm and beyond. It is possible to make some extrapolation, however, and our measured increase in attenuation of 100 - 300 dB/km for a 200 Gy accumulation is consistent with observations of other Quartz & Silice silica core fibers.

A final note of caution is in order here. We cannot discount the possibility that our observations on the test cell fiber are due at least in part to mechanical damage suffered after installation. The fiber route is the site of frequent movement of large, very heavy objects. However, we believe that the spectral structure of the attenuation argues for radiation damage. As soon as our observations are done, we shall sacrifice the fiber and critically examine the 7 m above the floor. Obviously, this will end the long-term observations.

3 Numerical Aperture Measurements

The numerical aperture (NA) of a fiber loosely is defined as the sine of the half-angle of the cone of emitted light when the fiber is optically filled.⁸ Values of NA of 0.25 to 0.4 are quoted for SiO_2 fibers, corresponding to an exit cone half-angle of 14 degrees to 24 degrees. We will use the half-height at half-maximum of the fiber's angular bandpass to define this number in the following discussion.

Total internal reflectance of the fiber's core-cladding interface sets the upper bound to the NA. We wondered if damage to the cladding or the cladding-core interface might be reflected in a reduced NA. For larger angles of incidence, a ray strikes the cladding interface more often, and enhanced absorption of the evanescent wave in the cladding would attenuate this ray more strongly than a near-axial ray.

The polymer cladding material used on our fibers is known to suffer radiation damage. Friebele cites work in his review that shows that 10^4 Gy causes embrittlement of the cladding.⁷ Observable damage to the optical properties should occur at a much lower level, perhaps at the 200 Gy level our loop has experienced.

The numerical aperture was measured with the same detector arrangement described above.

Figure 6 – The normalized transmission curves for the two reference fibers (1.6 m and 36 m) and the 104 m fiber loop that runs to the Test Cell and back, plotted as a function of the input angle of the parallel light source. The curves are all symmetric about the origin; for this figure they have been folded over at 0 degrees, and data from both positive and negative angles are included. If we define the numerical aperture as being measured to the half-height points, the reference fibers have $NA_{\text{short}} = 0.38$, $NA_{\text{long}} = 0.35$, and the damaged fiber has $NA_{\text{TC}} = 0.27$.

the measured transmission in the red, compared to that of the short fiber, is 42%. However, we know there is some loss of transmission in undamaged fibers, as shown by the 80% transmission of the 36 m reference fiber. The next step, therefore, is to ask whether the *added* attenuation from radiation of the damaged fiber can be accounted for by the loss of NA. Using the attenuation coefficients determined by the undamaged fibers, we extrapolate to a transmission of an undamaged 104 m fiber of 51% in the red. This means that the decrease in the NA, combined with the measured bulk attenuation of the undamaged fiber, predicts a total transmission of 39% for the damaged fiber in the red, very close to the measured value of 42%.

This extrapolation assumes that the LED fills the fiber input angles uniformly in the transmission tests. The red LED has a wide emission angle, and the fiber is butted against the diffuser housing of the diode, so we may not be too far from that situation. Incomplete filling of the fiber would cause us to overestimate the transmission of the damaged fiber, because we would not be measuring the transmission out to the higher input angles where we know it is selectively reduced.

We also have considered the fact that rays at a larger input angle travel further. This is a natural mechanism decreasing the NA of undamaged fibers. It appears, however, that this effect is not sufficient to explain an NA of 0.27 for the 104 m fiber.

This is about as far as we can go now. As we mentioned above, we plan to sacrifice the Test Cell fiber to examine more carefully the location of the damaged region. At that time, we plan to measure the NA of the 3 fibers relative to each other, so that the transmission of those rays at 0 degrees input angle can be compared. We will then try to determine if the radiation induced attenuation and numerical aperture change after full relaxation or self-annealing is due to damage in the cladding or cladding/core interface, as this preliminary work suggests.

For the input we used a He - Ne laser with a beam expander adjusted for a highly collimated beam larger than the fiber end face. The fiber was clamped with its face on the axis of a rotary stage on an optical bench. The detector signal was measured as a function of input angle on both sides of normal. A check for polarization effects found them to be unimportant over the range of angles measured.

Figure 6 shows the normalized NA plots for the 3 fibers.

The numerical aperture of the fibers shows a large change going from the reference fibers to the damaged fiber. At first look, however, it seems that the reduction of the NA in the damaged fiber is insufficient to account for the loss in transmission shown in Fig. 4. While the area under the damaged fiber's normalized NA curve is 71% of that of the short fiber,

As an added note, we would like to point out that it is not likely that the configuration of the Test Cell fiber is to blame for the reduced NA. Although the long fiber follows a tortuous path from the data acquisition room to the Test Cell, it is never bent more sharply than to a radius of 15 cm. The fiber is encased in a 2.5 cm diameter CorrLok™ flexible conduit, which prevents a sharper bend. We mention this because it is well known that bending reduces the NA of fibers, as rays intersect the bent fiber at angles too acute for internal reflection, and are lost. Figure 7 shows measurements we have done on the short (1.6 m) fiber.

Using the short reference fiber, which has an unbent NA of 0.38 (see Fig. 6), we adjusted the laser input angle to the half-height point on the transmission vs angle curve. At this operating point, a very small change in the NA will give a large shift in output signal. This change, multiplied by the slope of the curve in Fig. 6, gives the change in input angle at the

Figure 7- The numerical aperture of the 1.6 m reference fiber as a function of the bend radius. The NA was measured by setting the input angle of the expanded laser beam at the steepest point of the curve shown in Fig. 6, then bending the fiber and measuring the change in signal. This slope detection allows a very sensitive measurement of the change in NA, and accounts for the small error bars. The solid curve is a fit to the data of the predicted behavior from Eq. 5). We can see that a bend radius of 15 cm, the minimum allowed by the Test Cell fiber's conduit, will not seriously affect the NA of the fiber, and cannot account for the changes shown in Fig. 6.

the un-bent fiber, and is 1.40 for these fibers. In Fig. 7, we see a best fit to the bent-fiber NA data, which occurs for a value $x = 0.5$ mm. If this seems a large value for a 0.6 mm fiber, recall that we are already at such an acute input angle (halfway down the transmission vs angle curve) that half of the rays are lost. This preferentially transmits rays which enter a bend on the outside of the curve (a large value of x in this geometry) since they strike the cladding soonest, and, hence, at a less acute angle.

half-height point, which can be converted to a change in NA. The fiber was wrapped 360 degrees around cylinders of various diameter and the data in Fig. 7 were taken. The exact shape of a transmission vs angle response curve is very involved to calculate because of the contributions of the skew rays, rays that do not lie in a plane that includes the fiber axis. A calculation which includes only meridional rays predicts that the shape of the curve is given by⁸

$$5) \quad NA = \sqrt{n_1^2 - n_2^2 \left(\frac{R+d}{R+x} \right)^2}$$

where n_1 is the optical index of the core (1.45 for SiO₂ in the red), n_2 is the index of the polymer cladding, R is the radius of the bend, d is the diameter of the fiber, and x is the effective distance from the edge of the fiber to the point at which the ray is being injected. (Meridional rays lie in a plane which includes the fiber axis.) The value for n_2 is determined from the NA of

4 Attempts to Photobleach the Damaged Fibers

Photobleaching the damaged fiber to restore transmission is an attractive notion, since it can be done in the relative convenience of the data acquisition room away from the tokamak. When we measured incremental attenuations of some 100 - 300 dB/km in the damaged fiber, we decided to see whether our damage induced attenuation could be reduced by bleaching the damage sites with low-power laser light.

The literature on photobleaching is not entirely consistent. For an oversight of photobleaching work, see the review by Sigel.⁹ Friebele has reported significant bleaching at microwatt power levels.¹⁰ There is even a report that the bleaching effect is transient, which is an unsettling thought.¹¹

We used a He - Ne laser with a measured CW power level of 2 mW. The He - Ne wavelength of 633 nm falls in the middle of the non-bridging oxygen defect absorption/fluorescence band, which we have previously observed in this fiber.^{12, 1} The red LED is a good probe of transmission in that wavelength region.

For our first attempt, we simply pointed the laser beam (diameter about 2.5 mm) at the end of the 600 μ m core fiber, since Friebele has reported effects at very low power levels.¹⁰ After about 1 hour, we measured the transmission, and found no change within our measurement accuracy (about 5 %). Next we used a microscope objective to focus the entire laser beam on the fiber end face. After an hour of this we still saw no change.

We plan to extend these studies to higher power lasers, but the present results are not encouraging. It appears that photobleaching fibers with this level and type of damage will not be as simple as we had hoped.

A careful reading of the literature suggests that this result is not unexpected, however.⁹ As we have noted, we are observing the equilibrium damage level of attenuation. The current theory of photobleaching suggests a mechanism similar to that of self annealing, and data show that the limits of photobleaching are the same as those for annealing, leaving the same residue of nonremovable damage. However, immediately after the damage and before the self-annealing, we might expect that the transient darkening we reported in our earlier paper would decay even faster in the presence of a bleaching source.¹ It should be possible, by the counter injection of a bleaching beam in the fiber with a beam splitter (at a wavelength outside our signal band), to keep the transient attenuation down to a negligible level. This procedure would leave only the permanent damage, which will build up monotonically and more slowly, and which we would hope to account for by periodic re-calibrations.

5 Discussion

The attenuation results reported above are serious enough to cause problems in signal loss for the D - T phase of TFTR and JET (and will be intolerable in a much more reactive machine such as the proposed big international tokamak, ITER). There are several possible remedies for the current generation of fusion devices in their D - T phase of operation, both for attenuation and for the fluorescence reported earlier.¹ Fiber runs in the tokamak chamber should be kept very short, and should be shielded. The signal might be chopped at the source end, to allow fluorescence measurements to be made during the source-blocked phase. This technique decreases the average signal, however, and moving anything in a 5 T field in high

radiation is not an attractive idea. (We are nevertheless looking into the possibility.) A more promising idea is companion fibers cut from the same batch as the signal fibers. These companion fibers, which would run alongside the signal fibers and dead-end in opaque caps at the tokamak, would furnish a subtractable fluorescent signal. A more complicated (but perhaps necessary) method would be to use companion *loops*, carrying a square-wave light signal as we did for the transient opacity studies reported earlier.¹ The light-off phase supplies the fluorescent background, and the difference between light-on and light-off measures the changing transmission.

Our attempt at photobleaching seems to show that the equilibrium level of damage-induced attenuation cannot be lessened. On the other hand, the hope remains that the continuous injection of a bleaching signal might serve to eliminate the serious problem of the opacity changing on the same time scale that the plasma discharge evolves.

These remediation efforts are fairly simple, but some questions remain. If the NA of a system will be changing, it may be necessary to redesign some of the optical systems with this possibility in mind. Also, the predominant mechanism causing fluorescence is thought to be Cerenkov radiation arising from fast (Compton) electrons produced externally to the fiber.⁷ However, there is probably a direct excitation from gamma rays, too. The balance of these effects determines the nature of the fiber shielding which probably must be used for critical low-level signal fibers. We hope to examine these matters further.

Acknowledgments

We would like to thank L. Guttadora for the LED chopper, and J. Nichols for the preparation of the fibers for measurement. Conversations on optical matters with J. Bartolick were most helpful. D. Jassby furnished the integrated neutron dose, and conversations with L. P. Ku helped in the conversion of integrated neutron emission into a total radiation dose. This work was supported by U. S. Department of Energy Contract No. DE-AC02-76-CHO-3073.

References

1. A. T. Ramsey and K. W. Hill, "Nuclear Radiation Effects on Fused SiO₂ Lightguides," *Rev. Sci. Instrum.* **63**, 4735-4737 (1992).
2. P. D. Morgan, "Irradiation of Optical Fibres at JET through 14 MeV Neutron Production," *Proceedings of the Symposium on Fusion Technology*, 14-18/09/1992 (1992).
3. A. T. Ramsey and S. L. Turner, "HAIFA: A modular, fiber-optic coupled, spectroscopic diagnostic for plasmas," *Rev. Sci. Instrum.* **58**, 1211-1220 (1987).
4. K. Kadota, M. Otsuka and J. Fujita, "Space- and Time-Resolved Study of Impurities by Visible Spectroscopy in the High-Density Regime of JIPP T-II Tokamak Plasma," *Nucl. Fusion* **20**, 209-212 (1980).
5. S. Karasawa, *et al.*, "Fiber Optic Signal Attenuation by Secondary Ionizing Radiation in Nuclear Environments," *IEEE Trans. Nucl. Sci.* **NS-34**, 1105-1109 (1987).
6. J. G. Kolibal, L. P. Ku and S. L. Liew, "Two Dimensional Prompt Radiation Analyses for the TFTR", Princeton Plasma Physics Laboratory, Report EAD-R-33 (1985).
7. E. J. Friebele, *et al.*, "Overview of Radiation Effects in Fiber Optics," edited by P. W. Levy, *Proceedings of the SPIE Conference on Radiation Effects in Optical Materials*, SPIE **541**, 70-88 (1985).
8. W. P. Siegmund, "Fiber Optics", in *Handbook of Optics* (ed. W. G. Driscoll), page 13-6 (McGraw-Hill, New York, 1978).
9. G. H. Sigel, *et al.*, "An Analysis of Photobleaching Techniques for the Radiation Hardening of Fiber Optic Data Links," *IEEE Trans. Nucl. Sci.* **NS-28**, 4095-4101 (1981).
10. E. J. Friebele and M. E. Gingerich, "Photobleaching effects in optical fiber waveguides," *Appl. Optics* **20**, 3448-3452 (1981).
11. E. M. Dianov, *et al.*, "Reversible optical bleaching of the induced absorption in fiber-optic waveguides," *Sov. J. Quantum Electron.* **9**, 636-637 (1979).
12. G. H. Sigel and M. J. Marrone, "Photoluminescence in As-drawn and Irradiated Silica Optical Fibers: An Assessment of the Role of Non-bridging Oxygen Defect Centers," *J. Non-Crys. Sol.* **45**, 253-247 (1981).

EXTERNAL DISTRIBUTION IN ADDITION TO UC-420

Dr. F. Paoloni, Univ. of Wollongong, AUSTRALIA
 Prof. M.H. Brennan, Univ. of Sydney, AUSTRALIA
 Plasma Research Lab., Australian Nat. Univ., AUSTRALIA
 Prof. I.R. Jones, Flinders Univ, AUSTRALIA
 Prof. F. Cap, Inst. for Theoretical Physics, AUSTRIA
 Prof. M. Heindler, Institut für Theoretische Physik, AUSTRIA
 Prof. M. Goossens, Astronomisch Instituut, BELGIUM
 Ecole Royale Militaire, Lab. de Phy. Plasmas, BELGIUM
 Commission-Européenne, DG. XII-Fusion Prog., BELGIUM
 Prof. R. Bouciqué, Rijksuniversiteit Gent, BELGIUM
 Dr. P.H. Sakanaka, Instituto Fisica, BRAZIL
 Instituto Nacional De Pesquisas Espaciais-INPE, BRAZIL
 Documents Office, Atomic Energy of Canada Ltd., CANADA
 Dr. M.P. Bachynski, MPB Technologies, Inc., CANADA
 Dr. H.M. Skarsgard, Univ. of Saskatchewan, CANADA
 Prof. J. Teichmann, Univ. of Montreal, CANADA
 Prof. S.R. Sreenivasan, Univ. of Calgary, CANADA
 Prof. T.W. Johnston, INRS-Energie, CANADA
 Dr. R. Bolton, Centre canadien de fusion magnétique, CANADA
 Dr. C.R. James,, Univ. of Alberta, CANADA
 Dr. P. Lukác, Komenského Univerzita, CZECHO-SLOVAKIA
 The Librarian, Culham Laboratory, ENGLAND
 Library, R61, Rutherford Appleton Laboratory, ENGLAND
 Mrs. S.A. Hutchinson, JET Library, ENGLAND
 Dr. S.C. Sharma, Univ. of South Pacific, FIJI ISLANDS
 P. Mähönen, Univ. of Helsinki, FINLAND
 Prof. M.N. Bussac, Ecole Polytechnique,, FRANCE
 C. Moutet, Lab. de Physique des Milieux Ionisés, FRANCE
 J. Radet, CEN/CADARACHE - Bat 506, FRANCE
 Prof. E. Economou, Univ. of Crete, GREECE
 Ms. C. Rinni, Univ. of Ioannina, GREECE
 Dr. T. Mui, Academy Bibliographic Ser., HONG KONG
 Preprint Library, Hungarian Academy of Sci., HUNGARY
 Dr. B. DasGupta, Saha Inst. of Nuclear Physics, INDIA
 Dr. P. Kaw, Inst. for Plasma Research, INDIA
 Dr. P. Rosenau, Israel Inst. of Technology, ISRAEL
 Librarian, International Center for Theo Physics, ITALY
 Miss C. De Palo, Associazione EURATOM-ENEA, ITALY
 Dr. G. Grosso, Istituto di Fisica del Plasma, ITALY
 Prof. G. Rostangini, Istituto Gas Ionizzati Del Cnr, ITALY
 Dr. H. Yamato, Toshiba Res & Devel Center, JAPAN
 Prof. I. Kawakami, Hiroshima Univ., JAPAN
 Prof. K. Nishikawa, Hiroshima Univ., JAPAN
 Director, Japan Atomic Energy Research Inst., JAPAN
 Prof. S. Itoh, Kyushu Univ., JAPAN
 Research Info. Ctr., National Inst. for Fusion Science, JAPAN
 Prof. S. Tanaka, Kyoto Univ., JAPAN
 Library, Kyoto Univ., JAPAN
 Prof. N. Inoue, Univ. of Tokyo, JAPAN
 Secretary, Plasma Section, Electrotechnical Lab., JAPAN
 S. Mori, Technical Advisor, JAERI, JAPAN
 Dr. O. Mitarai, Kumamoto Inst. of Technology, JAPAN
 J. Hyson-Sook, Korea Atomic Energy Research Inst., KOREA
 D.I. Choi, The Korea Adv. Inst. of Sci. & Tech., KOREA
 Prof. B.S. Liley, Univ. of Waikato, NEW ZEALAND
 Inst of Physics, Chinese Acad Sci PEOPLE'S REP. OF CHINA
 Library, Inst. of Plasma Physics, PEOPLE'S REP. OF CHINA
 Tsinghua Univ. Library, PEOPLE'S REPUBLIC OF CHINA
 Z. Li, S.W. Inst Physics, PEOPLE'S REPUBLIC OF CHINA
 Prof. J.A.C. Cabral, Instituto Superior Tecnico, PORTUGAL
 Dr. O. Petrus, AL I CUZA Univ., ROMANIA
 Dr. J. de Villiers, Fusion Studies, AEC, S. AFRICA
 Prof. M.A. Hellberg, Univ. of Natal, S. AFRICA
 Prof. D.E. Kim, Pohang Inst. of Sci. & Tech., SO. KOREA
 Prof. C.I.E.M.A.T, Fusion Division Library, SPAIN
 Dr. L. Stenflo, Univ. of UMEA, SWEDEN
 Library, Royal Inst. of Technology, SWEDEN
 Prof. H. Wilhelmson, Chalmers Univ. of Tech., SWEDEN
 Centre Phys. Des Plasmas, Ecole Polytech, SWITZERLAND
 Bibliotheek, Inst. Voor Plasma-Fysica, THE NETHERLANDS
 Asst. Prof. Dr. S. Cakir, Middle East Tech. Univ., TURKEY
 Dr. V.A. Glukhikh, Sci. Res. Inst. Electrophys. I Apparatus, USSR
 Dr. D.D. Ryutov, Siberian Branch of Academy of Sci., USSR
 Dr. G.A. Eliseev, I.V. Kurchatov Inst., USSR
 Librarian, The Ukr.SSR Academy of Sciences, USSR
 Dr. L.M. Kovrizhnykh, Inst. of General Physics, USSR
 Kernforschungsanlage GmbH, Zentralbibliothek, W. GERMANY
 Bibliothek, Inst. Für Plasmaforschung, W. GERMANY
 Prof. K. Schindler, Ruhr-Universität Bochum, W. GERMANY
 Dr. F. Wagner, (ASDEX), Max-Planck-Institut, W. GERMANY
 Librarian, Max-Planck-Institut, W. GERMANY
 Prof. R.K. Janev, Inst. of Physics, YUGOSLAVIA

END

DATE
FILMED

4 / 28 / 93