2. U.S. DOE Patent Clearance is not required prior to the publication of this document.

DOE/PC/91299-T4 RECEIVED

NOV 06 1992

COMBINED
ANNUAL TECHNICAL PROGRESS REPORT
FOR PERIOD 9/01/91 TO 8/31/92
and
QUARTERLY TECHNICAL PROGRESS REPORT
FOR PERIOD 7/1/92 TO 9/30/92

DOE/PC/91299--T4
DE93 007622

on DOE/PETC Grant No. DE-FG22-91-PC91299

"Magnetic Relaxation - Coal Swelling, Extraction, Pore Size"

David C. Doetschman, Principal Investigator

Department of Chemistry, State University of NY, Binghamton, NY, 13902-6000

Progress Summary

The goals for year I of the grant were to extract the Argonne Coals, to swell them, to reswell their residues, to seal the various samples for measurements, to perform analyses of the samples and to measure their NMR decays. Because of an unexpected characteristic of the extraction process, more detailed analyses of the samples are being done than originally anticipated. The mass spectrometric analyses have not been completed. Because routine NMR analyses needed to be done in greater detail than anticipated, the NMR decay measurements have also been delayed. In order to offset these delays, all of the EPR samples, which were to have been examined in year III, have been prepared and a substantial proportion of the pulsed EPR measurements have been made. Some of the extraction results have been included in a publication on another topic¹ (Appendix I). The pulsed EPR characteristics of the whole coals that were planned are included in a paper accepted for publication on a detailed pulsed EPR analysis of the Argonne coals² (Appendix II).

Extraction of the Coals

The well-known protocols for the extraction of coals with CS₂ and N-methyl-2-pyrrolidinone (NMP) include acetone washes of the extract and residue.^{3,4} The parts of the protocol that call for the acetone washes were omitted for the following reason. The aim of the project is to understand the physical aspects of the extraction process in terms of the mobile and immobile molecular species in the coal, in terms of coal swelling and in terms of pore structure. Therefore from the physical standpoint we found it to be undesirable to employ another chemical agent (i.e. acetone) which has been shown also to be capable of extracting material from the coal or residue.⁵

The samples of the whole coal, as received, were dried and the resulting samples of extract and residue were evacuated at 145°C with a mechanical, rotary vacuum pump and N₂(l) cold trap for 6-24 hours until they reached weights constant to one percent. The ultrasonic extraction, centrifugation and filtration steps were all carried out either in oxygen-free N₂(g)-flushed (prepure grade) containers or in a similarly flushed glove box. The temperature of 145°C for the removal of solvent from the extract and residue and drying of the whole coals under vacuum was

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

chosen because it was the lowest temperature at which constant sample weight could be achieved in a time of less than two days heating under vacuum. It is well-known that it is common practice to dry coals at significantly lower temperatures than this and that various degrees of non-covalent bond rearrangement of the coal structure occur at or below a temperature of 145°C. Some of these kinds of rearrangements have probably actually begun with the removal of water in the drying step. Since the NMP from the CS₂/NMP binary solvent was bound, presumably non-covalently, so tightly as to require heating to 145°C, our assessment was that this process could not be appreciably worse than the drying and CS₂/NMP extraction steps themselves. It should be noted that any conclusions to be drawn from this study will apply, strictly speaking, only to the properties of the materials as they exist after heating to 145°C and not necessarily to these properties in native coals at ambient or other different conditions.

The extraction results by weight and some of the analyses, to be discussed in greater detail next, show that appreciable amounts of NMP are retained in the residues and extracts of the coals. The sums of the weights of the residues and extracts were found to exceed the original weights of the whole coals in all cases for which we made measurements. The results on an organic matter basis are presented in Figure 1 for seven of the coals. Recovery of the Beulah Zap residue was not quantitative and has been omitted from Figure 1.

In Figure 2 are shown the percentages by weight of NMP in the extracts determined from the NMR spectra of pyridine-d₅ solutions of the extracts in comparison with a standard NMP solution in pyridine-d₅. In Figure 3 are shown the percentages of acetone washable NMP by weight based on the organic matter in the residues, likewise determined in acetone-d₆ solution in comparison with a standard NMP solution in acetone-d₆.

There is an excellent correspondence between the trends in the relative amounts of NMP in the extracts (Figure 2) and the trends in the relative amounts of NMP that can be washed from the residues (Figure 3). The extracts displaying the largest NMP contents (Illinois No. 6, Pittsburgh No. 8, Lewiston Stockton and Pocahontas) were also the only coals with an obvious NMP carbonyl stretch peak at ca. 1670 cm⁻¹ in the IR spectra. There is also a good correspondence between these trends and the trends in the percentages by weight of solvent retained (Figure 1) for most of the coals, the Wyodak Anderson coal being the most obvious exception. The same discrepancy, that is so obvious in the Wyodak Anderson coal, between the NMP retained by weight and the amounts present in the extract and washable from the residue, upon closer examination, is also found to be present in several of the other coals. The actual percentages of NMP in the extracts and residue washings of the Pocahontas, Lewiston Stockton and Blind Canyon coals appear to be in line with the percent NMP retained by weight. However, the sums of the percentages of NMP in the extracts and residue washings of the Upper Freeport, Pittsburgh No. 8, Illinois No. 6 and Wyodak Anderson coals fall short of the percentages of NMP retained by weight. The discrepancies (aside from the exceptions of the Blind Canyon and Lewiston Stockton coals) tend to increase with decreasing coal rank.⁶ The results suggest that there is an increasing tendency with decreasing coal rank for NMP to be retained so tightly in the residue that prolonged heat treatment at 145°C and acetone washing cannot remove it. It is possible that it is an increasing tendency for some coals to hydrogen bond to NMP with decreasing coal rank that is responsible for these observations.

On the basis of the yield by weight of extract and residue, the total NMP retained (Figure 1) and the percent NMP found in the extract (Figure 2), the extract and residue yields on an NMP-free basis have been calculated and are presented in Table 1 for all of the coals for which sufficient data was obtained.

Analysis of the Extracts

The IR spectra of the extracts display the kinds of trends with coal rank that are generally expected. The aromatic C-H out-of-plane bending and C-C stretching bands are observed to increase with the rank of the parent coal above about 80% carbon but are weak and not clearly identifiable in the extracts of coals of lower rank. This is in accord with increasing aromaticity of the parent coal with increasing rank. The methyl and methylene C-H stretching peaks in the extracts of all eight coals are observable and have intensities that decrease with parent coal rank. Also noteworthy is the fact that the ratio of methyl to methylene C-H stretching peak intensities appear to increase with coal rank. This suggests that, as the aliphatic nature of the coal extracts increase with decreasing parent coal rank, there is a tendency toward longer chains with relatively more methylene groups per chain (usually terminated with a methyl group). A broad band of C-O stretching modes, superimposed by that of NMP in some of the coal extracts, is found between 1550 cm^{-1} and 1750 cm^{-1} throughout the range of extracts. The broad band exhibits relatively subtle changes in shape from one sample to another and is probably from a variety of functional groups that contain the C=O group. The overall intensity of the broad C-O stretching band appears to be more a function of the particular coal than a function of parent coal rank. The absence of the strong, sharp C-O stretching peak characteristic of coal air-oxidation is missing in all samples, presumably because of the oxygen-free extraction and sample preparation. The fact that the broad, weak C-O peaks are observed in the extracts of all of the coals probably reflects the strong ability of the NMP in the solvent to extract the molecules with polar functional groups, across the range of coal ranks.

The solution proton NMR spectra of the extracts exhibit broad lines or bands in the aromatic(7-8 ppm) and aliphatic(2.2-3 ppm) regions. Because of the breadths of the bands, the intensities are weak relative even to the impurity proton NMR peaks in the NMR grade deuterated solvents. Therefore quantitative integrations of these bands was not feasible, leaving only qualitative observations possible. Somewhat surprising to us was the fact that the relative intensities of the aromatic and aliphatic bands did not differ markedly through the range of ranks of parent coals. The intensity of the aromatic region, which is somewhat less obscured by solvent peaks than the aliphatic region, increases from a negligible level below 75% C in the parent coal to a maximum at around 85% C in the parent coal and decreases again to an undetectable level again above 89% C in the parent coal. The constant relative NMR intensities of the aliphatic and aromatic proton bands may reflect the particular extracting character of the solvent across the range of coal ranks. The intensity change in the extract spectrum with coal rank suggests that, as the coals increase in aromaticity, there is a corresponding increase in numbers of aromatic protons up to around 85% C in the parent coal. Then, as one progresses from the more aliphatic to the more aromatic coal beyond 85% C in the parent coal, the extracted molecules suffer not only a loss of aliphatic protons but also a comparable loss of aromatic protons as a result of aromatic ring condensation.

Pulsed EPR Measurements

The pulsed EPR measurements on the whole Argonne coals are being published² (Appendix II). It proved to be possible to measure separate relaxation times and numbers of spins in the inertinite maceral and in the other broad line macerals in the whole coals. The T_2 (spin-spin relaxation times) were a measure of spin-exchange between the free radicals in the inertinite maceral and a measure of dipolar interactions between the spins in the non-inertinite macerals. T_1 (the spin-lattice relaxation time), which depends on lattice modulation of the proton hyperfine interactions in the free radical molecules in all maceral types, appears to be a good index of the flexing of the coal matrix in which the free radicals are bound.

Measurements of the pulsed EPR characteristics of the extracts and residues from the eight Argonne coals are well under way. The T_1 of the whole coal maceral groups and the T_1 of the extracts and residues are compared in Table 2. The T_2 of the non-inertinite macerals in the whole coals and the T_2 of the extracts and residues are compared in Table 3. More work remains to be done in analyzing the T_2 and their uncertainties (T_2 is obtained by graphical extrapolation of T_2 to a low pulse spin turning angle limit). Table 4 gives the numbers of spins per gram of organic matter in the non-inertinite macerals of the whole coals and the relative numbers of spins per gram in the extracts and residues. Further work needs to be done to determine the absolute number of spins.

The spin-lattice relaxation rates appear to make good sense as indexes of the degree of flexing of the matrix of the free radical molecules. The extract relaxation times are comparable with the times of the non-inertinite macerals of the whole coals at low parent coal rank but become significantly less than those of the non-inertinite macerals at high rank. This suggests that the low rank, non-inertinite macerals are as "soft" as the solid extracts but the matrixes of high rank non-inertinite macerals are substantially more rigid than the solid extracts. This is probably a reflection of significantly more cross-linking and/or aromatic condensation in the high rank coals. In general, the T_1 of the residues are longer than the solid extracts supporting the idea that a more rigid molecular matrix is left behind in the residue when the extract molecules are removed. In general the residue T_1 times are shorter than the non-inertinite macerals from which they come, suggesting that the extraction process and perhaps the solvent retained have "softened up" the macromolecular matrix. The Blind Canyon and Pittsburgh No. 8 coals are interesting counter-examples in which it would appear that solvent extraction has left behind a more rigid matrix, perhaps through some special hydrogen bonding synergy between coal and retained solvent.

By-and-large the extract and residue spin-spin relaxation times are less than those of the whole coal and the residue T_2 are shorter than the extract T_2 . However, since the T_2 are probably determined by concentration-dependent dipolar interactions², a full analysis of these data cannot be done without completing the spin concentration analysis.

At this stage of the analysis we see few uniform trends in the numbers of spins per gram in the whole coals, extracts and residues, nor are we in a position to check the conservation of spins in the extraction process. Although there are some exceptions, the tendency for the number of spins per gram to increase with increasing coal rank in the whole coals is reflected in the residues. However, this tendency does not appear to carry over as strongly, if at all, to the extracts where the high rank Upper Freeport and Pocahontas No. 3 coal extracts have equal or fewer numbers of

spins per gram than the mid-rank Blind Canyon, Pittsburgh No. 8 and Lewiston Stockton coals. These results suggest that the free radicals are increasingly associated with the macromolecular matrix that is left behind in the residue as the rank of the coal increases

Proton NMR Relaxation Measurements

We have begun to explore the types of measurements that we need to make in order to facilitate the analysis of the T_1 of the samples of the solid whole coal, extract and residue. To do so we have focused our attention initially on the Upper Freeport whole coal sample. We have been using a π - τ - $\pi/2$ inversion recovery sequence, after which the free-induction-decay (FID) of the $\pi/2$ pulse is acquired and Fourier transformed. Figure 4 shows the $\tau = 50 \mu\text{sec}$ spectrum. The spectrum comprises three distinct lines. There is a very sharp line at about 10 ppm, whose T_1 is about 15 msec, which is inverted in Figure 4. Then there is a line of ca. 12 ppm width, also centered at ca. 10 ppm, whose T_1 is so short ($\ll 50 \mu\text{sec}$) that no indication of saturation was observed at $\tau = 50 \mu\text{sec}$. Thirdly, there is a very broad line of 80 - 100 ppm observed width. (The actual width may be different and probably broader because of H_1 limitations.) The broad line is inverted in Figure 4. The recovery of the broad line is biphasic with one $T_1 = 485 (\pm 41)$ msec and with another, faster decay with $T_1 \sim 75$ msec. If H_1 is less than the width of the broad NMR line, it is possible that this faster decaying component is contaminated with some spin diffusion (T_2) processes.

We have developed satisfactory methods of analyzing the saturation recovery of the broad NMR line but we are still working on appropriate data acquisition methods to permit an analysis of the recovery of the sharp line. We believe that several components in this spectrum may be related to the maceral types present in the whole coal. This preliminary exercise on the whole coal should prepare us well for the extract and residue analyses except for the possible complications of retained solvent.

References

1. D. C. Doetschman, E. Ito, O. Ito and H. Kameyama, *Energy & Fuels* **6**, 635 (1992).
2. D. C. Doetschman and D. W. Dwyer, *Energy & Fuels*, accepted for publication.
3. M. Iino, T. Takanohashi, H. Ohsuga and K. Toda, *Fuel* **67**, 1639 (1988).
4. W. A. Barton, O Ito and L. J. Lynch, *Proceedings of the Australian Coal Science Conference, Japan-Australia Joint Research Program for the Development of Efficient Conversion Processes for Victoria Brown Coal*, 1989.
5. T. Takanohashi and M. Iino, *Energy & Fuels* **4**, 452 (1990).
6. K. S. Vorres, *Energy & Fuels* **4**, 420 (1990).

Table 1. The dmmf yields by weight of extract and residue after correction for NMP retained.

Coal	Extract Yield (%)	Residue Yield (%)
Wyodak Anderson	36.8	63.2
Illinois No. 6	54.0	46.0
Blind Canyon	38.8	61.2
Pittsburgh No. 8	54.8	45.2
Lewiston Stockton	27.9	72.1
Upper Freeport	90.2	9.8
Pocahontas No. 3	18.2	81.8

Table 2. The spin-lattice relaxation times T_1 of the Argonne Premium coal maceral groups in the whole coal and the T_1 of the extracts and residues of the coals. The T_1 of the weak, narrow inertinite lines that are also observed in the residues, have not yet been measured. Uncertainties are given in parentheses, where measured.

Coal	T_1 , sec			
	Whole Coal		Extract	Residue
	Inertinite ^{a,b}	Other Macerals ^{a,b}		
Beulah Zap	----	24	31.2(0.2)	22.82(0.03)
Wyodak Anderson	----	27	16.11(0.03)	21.45(0.04)
Illinois No. 6	390	64	36.77(0.03)	46.18(0.09)
Blind Canyon	----	15	33.48(0.04)	36.8(0.4)
Pittsburgh No. 8	----	17	45.0(0.2)	52.10(0.05)
Lewiston Stockton	500	74	46.82(0.06)	34.05(0.07)
Upper Freeport	490	160	39.92(0.05)	53.3(1.8)
Pocahontas No. 3	480	130	27.5(0.1)	69.1(1.5)

^a From reference 2.

^b Uncertainties were estimated to be less than 10% of the values given, except for the Pocahontas coal No. 3 inertinite value for which the uncertainty is 20%.

Table 3. The spin-spin relaxation times T_2 of the non-inertinite macerals of the whole Argonne Premium coals and of their extracts and residues. Uncertainties are given in parentheses, where measured.

Coal	T_2 (sec)		
	Whole Coal Non-Inertinite Macerals	Extract	Residue
Beulah Zap	1020(160)	1580	370
Wyodak Anderson	1340(160)	1170	710
Illinois No. 6	464(35)	3900	1270
Blind Canyon	950(100)	2140	890
Pittsburgh No. 8	355.8(8.8)	4760	1680
Lewiston Stockton	1450(110)	2340	820
Upper Freeport	390(20)	2780	2640
Pocahontas No. 3	507(54)	1590	1200

Table 4. Spins per gram of organic matter in the non-inertinite organic matter in the whole coals and the relative numbers of spins per gram of the extracts and residues. Spins of the narrow inertinite line of the residues are not included.

Coal	Spins per gram x 10 ⁻¹⁹		
	Whole Coal	Relative Values	
	Non-Inertinite Macerals	Extract ^a	Residue ^{a,b}
Beulah Zap	0.93	1	0.65
Wyodak Anderson	0.89	0.60	0.95
Illinois No. 6	2.6	2.53	1.66
Blind Canyon	2.1	1.53	2.68
Pittsburgh No. 8	3.6	2.59	2.58
Lewiston Stockton	10 ^c	2.38	1.48
Upper Freeport	5.6	0.56	1.98
Pocahontas No. 3	19 ^c	1.53	2.76

^a Uncorrected for solvent retention and differences in echo decay.

^b Uncorrected for mineral matter content.

^c Probably overestimated. See reference 2.

Figure Captions

1. Plots of points displaying the total solvent retained on a weight percentage basis in the NMP/CS₂ extraction of seven of the eight Argonne Premium Coal samples as a function of the percent carbon in the organic matter of the whole coal. (Omission of the Beulah Zap coal is explained in the text.) Solvent retained is presented as a percentage of weight relative to the organic matter in the whole coal and is defined as $[(R+E-W)/W] \times 100\%$, where R, E and W are the dmmf weights of the organic matter in the residue, extract and whole coal, respectively. It is assumed the mineral matter is retained entirely in the residue. W and the ash content are calculated from the dry weights of the whole coal and its ash percentage. R is calculated from the dry weights of the whole coal and the ash content of the whole coal. E is the measured weight of the extract.
2. Percent by weight of NMP found by NMR analysis in the extracts of seven of the eight Argonne coals as a function of the percent carbon in the organic matter of the whole coal. The Beulah Zap extraction yield was too small to perform this experiment.
3. Percent by weight of NMP found by NMR analysis in the acetone washing of the residues of seven of the eight Argonne coals as a function of percent carbon in the organic matter of the whole coal.
4. NMR spectrum of the Upper Freeport whole coal obtained from the Fourier transformation of the FID after the $\pi/2$ pulse in a π - τ - $\pi/2$ saturation recovery sequence at $\tau = 50 \mu \text{ sec}$.

Figure 1

Percent NMP in Extracts vs. Percent Carbon by NMR

Figure 2

Figure 3

Percent NMP washed from Residues vs. Percent Carbon
by NMR

based on Organic matter in Residue

Figure 4.

VD=.00005 COAL 101

-137.928

-121.823

-78.232

-9.849

6.393

9.801

11.761

21.292

112.158

144.680

173.350
183.070
PPM

END

**DATE
FILMED**

3 / 16 / 93