ORNL/ER--142

DE93 006363

Energy Systems Environmental Restoration Program
ORNL Environmental Restoration Program

**Feasibility Study on the Solidification of Liquid Low-Level Radioactive
Mixed Waste in the Inactive Tank System at Oak Ridge
National Laboratory, Oak Ridge, Tennessee**

**S. Trussell
R. D. Spence**

Date Issued—January 1993

**Prepared by
Chemical Technology Division
Oak Ridge National Laboratory**

**Prepared for
U.S. Department of Energy
Office of Environmental Restoration and Waste Management
under budget and reporting code EW 20**

**OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U.S. DEPARTMENT OF ENERGY
under contract DE-AC05-84OR21400**

MASTER

EP

Author Affiliations

S. Trussell is a student in the Department of Civil Engineering at Texas A&M University, College Station. R. D. Spence is a member of the Chemical Technology Division, Oak Ridge National Laboratory, Martin Marietta Energy Systems, Inc.

CONTENTS

TABLES	v
EXECUTIVE SUMMARY	vii
1. INTRODUCTION	1
1.1 BACKGROUND	1
1.2 WASTE CHARACTERIZATION	1
1.3 TREATMENT ALTERNATIVES	3
1.4 REGULATORY CONSIDERATIONS	3
1.5 PURPOSE OF THIS STUDY	4
2. REVIEW OF RETARDATION MECHANISMS	5
2.1 INTRODUCTION	5
2.2 RETARDATION MECHANISMS	5
2.3 POSSIBLE RETARDERS IN THE WASTE	6
3. INORGANIC INTERACTIONS WITH CEMENT	7
3.1 INTRODUCTION	7
3.2 CHEMICAL SPECIATION OF METALS	7
3.3 EFFECTS OF METALS ON CEMENT HYDRATION	8
3.3.1 Lead	8
3.3.2 Zinc	8
3.3.3 Mercury	9
3.3.4 Others	9
3.4 EFFECTS OF ANIONS	9
3.5 CONCLUSIONS	9
4. ORGANIC INTERACTIONS WITH CEMENT	10
4.1 INTRODUCTION	10
4.2 ANALYTICAL PROBLEMS	11
4.3 SOLIDIFICATION/STABILIZATION OF ORGANICS WITH CEMENTITIOUS BINDERS	11
4.3.1 Physical Properties of Waste Forms	12
4.3.2 Leaching Properties of Waste Forms	12
4.3.3 Microstructural Properties of Waste Forms	14
4.4 PRETREATMENT OF ORGANICS WITH ORGANOPHILIC CLAYS	15
4.4.1 Chemical Reaction Mechanisms	15
4.4.2 Details of Specific Studies	16
4.4.3 Questions Surrounding Use of Organophilic Clays	16
4.5 CONCLUSIONS	18
5. MIXED WASTE INTERACTIONS WITH CEMENT	19
5.1 INTRODUCTION	19
5.2 PROBLEMS WITH SOLIDIFICATION OF MIXED WASTES	19

5.3 SOLUTIONS TO MIXED WASTE SOLIDIFICATION PROBLEMS	19
5.3.1 Hydration Effects	19
5.3.2 Radionuclide Retention	20
5.3.3 Radiolytic Gas Production	21
5.4 CONCLUSIONS	21
6. PRELIMINARY EXPERIMENTAL DESIGN	22
7. SUMMARY AND CONCLUSIONS	26
8. BIBLIOGRAPHY	27

TABLES

- 1 High lead or sulfate concentrations as reported in the waste
characterization report (ORNL 1992) 22
- 2 Preliminary list of variables for the tank wastes grout formulation 24

EXECUTIVE SUMMARY

A literature survey was conducted to help determine the feasibility of solidifying a liquid low-level radioactive mixed waste in the inactive tank system at Oak Ridge National Laboratory (ORNL). Several electronic data bases were searched. The search identified 78 relevant books, articles, and reports. Of these, 70 were acquired from the ORNL library or through interlibrary loans. The documents upon which this report is based include recent studies on the solidification/stabilization (S/S) of organics, inorganics, and radionuclides. Among the literature cited are four previous reviews pertaining to S/S of organics and two reviews of retardation mechanisms.

The goal of this report is to facilitate a decision on the disposition of these wastes by identifying any waste constituents that might (1) compromise the strength or stability of the waste form or (2) be highly leachable. Furthermore, its goal is to identify ways to circumvent interferences and to decrease the leachability of the waste constituents.

This study has sought to provide an understanding of inhibition of cement set by identifying the fundamental chemical mechanisms by which this inhibition takes place. From this fundamental information, it is possible to draw some conclusions about the potential effects of waste constituents, even in the absence of particular studies on specific compounds.

The sludges and liquids in the ORNL tanks contain materials known to interfere with the cementitious solidifying reactions, but current information can be used to tailor solidification formulations to overcome these interferences so that the sludges and liquids can be solidified. The main inorganic interferants are lead and sulfate, both of which have been solidified successfully at grout concentrations of <5 wt %. The low organic concentrations in the tanks have not hampered solidification in the past, although special additives such as organophilic clays may be warranted to help immobilize the organics. The separate oily phase in tanks WC-15 and WC-17 could pose a problem by coating solidification agent particles during mixing, but oils and oily layers have been solidified previously by emulsifying the oil or by using an additive to prevent the oil from interfering with the hydration reaction. Because the solidification formulations must be tailored to overcome interference effects, a single formulation will not necessarily perform well for all the tank sludges and liquids. Consequently, each tank must be tested individually with a proposed formulation and modifications made as necessary.

If the contents of more than one tank are combined prior to treatment, a formulation could be designed for the composite. This approach requires that the tank contents be well mixed to give a homogenous mass for treatment. Combining tank contents may be impracticable, however, for any number of reasons (e.g., no tank large enough to hold all of the sludge and liquid, prohibition by regulation or policy, or incompatible tank contents).

This report anticipates that a baseline formulation with which to test the contents of each tank would be desirable. More than one option exists for developing such a baseline formulation. One would be to develop a surrogate waste that incorporates all the worst features of the different tank contents (e.g., highest inorganic, organic, and radionuclide concentrations) and then develop a formulation for this surrogate. Another would be to select

one of the worse tank contents and develop a formulation based on the actual waste from the selected tank. Regardless of the approach, it must be emphasized that any such baseline formulation cannot be guaranteed to work for every tank. The baseline formulation would have to be tested with the actual wastes from each tank. A preliminary experimental design is presented for the development of such a baseline formulation.

1. INTRODUCTION

1.1 BACKGROUND

Oak Ridge National Laboratory (ORNL) was established in 1943 as a part of the Manhattan Project. Its facilities are located on the 58,000-acre Oak Ridge Reservation, which is owned by the federal government and operated under the jurisdiction of the Department of Energy (DOE). Over the years, ORNL has generated a wide variety of liquid radioactive, hazardous, and mixed wastes as a result of its research missions. Research activities have historically involved nuclear fuel reprocessing, radioisotope production, and testing and development related to nuclear reactor design. In recent years, the scope of the Laboratory's work has broadened to include biological, environmental, and materials research, and other energy-related areas of research.

An underground tank system to contain liquid low-level wastes (LLLW) from the laboratories was installed over the years. Many of these tanks are no longer in use. The oldest tanks in the inactive tank system are about 50 years old and the newest almost 30. They are located in the Bethel Valley north and south tank farms and elsewhere in the main laboratory area, and in Melton Valley near the old hydrofracture facility and the homogeneous reactor facility. Most of the inactive tanks have no secondary containment.

The largest of the tanks are made of gunite. Others are made of either carbon steel or stainless steel. Tank sizes range from 825 gal to 170,000 gal. The combined capacity of the 29 inactive tanks that have been sampled and tested thus far is over 1.2 million gallons. Actual waste volumes in the tanks are unknown but could be approximated from depth measurements and tank dimensions. Three tanks are empty, and one has not been located and may not have been installed.

The Oak Ridge Reservation was placed on the National Priorities List of sites in need of remediation under the provisions of the Comprehensive Environmental Response, Compensation, and Liability Act/Superfund Amendment and Reauthorization Act (CERCLA/SARA) in December 1989. The provisions of a subsequent Federal Facilities Agreement signed by DOE, Environmental Protection Agency (EPA), and Tennessee Department of Environment and Conservation (TDEC) effective January 1, 1992, mandate investigation and remediation of environmental impacts resulting from past operations on the Oak Ridge Reservation. This directive provides the impetus for the chemical characterization and treatment studies that will precede the ultimate disposal of the wastes in the inactive LLLW tank system.

1.2 WASTE CHARACTERIZATION

Chemical analyses have been performed on samples from 29 of the 54 inactive tanks (ORNL 1992). Many of the tanks contain both aqueous liquid and sludge layers. Some of the sludges are hard and others, soft. One tank contains a thin oily layer resembling 90-weight oil on top of the aqueous layer. Another contains an organic layer containing polychlorinated biphenyls (PCBs) on top of the aqueous layer. Some tanks contain only aqueous liquids and

no sludges. The profile of chemical elements and compounds include several anions; a number of heavy metals; many volatile and semivolatile organic compounds; and a wide variety of alpha-, beta-, and gamma-emitting radionuclides.

Metals. The metals most often appearing in the sludge layers at concentrations >75 ppm are Cr (16 tanks), Pb (14 tanks), and Ba (13 tanks). Three tanks have chromium and lead concentrations >1000 ppm; the highest of these is 14,000 ppm of lead in a hard sludge. Two tanks have barium concentrations >1000 ppm. The next most prevalent compounds occurring at concentrations >75 ppm are Ni (7 tanks), Hg (4 tanks), Cd (3 tanks), and U (5 tanks). Existing in measurable concentrations <75 ppm in both liquid and sludge layers are Cr (13 tanks), Pb (9 tanks), Ba (15 tanks), Ni (14 tanks), Hg (22 tanks), Cd (17 tanks), Ag (25 tanks), As (5 tanks), Se (2 tanks), and Tl (1 tank).

Anions. The only anions occurring in liquid layers at concentrations >1000 ppm are nitrate (5 tanks), phosphate (1 tank), and sulfate (2 tanks). The highest nitrate concentration is 25,000 ppm and occurs in one tank. The highest sulfate concentration is 83,000 ppm and occurs in one tank. Fluoride occurs in the sludges of three tanks at concentrations >1000 ppm.

Organics. These wastes contain a wide variety of volatile and semivolatile organics. Concentrations are on the order of fractional parts per million for most compounds in most tanks. The exceptions are as follows: At concentrations between 200 and 300 ppm, fluoranthene; between 100 and 200 ppm, bis(2-ethylhexyl) phthalate, di-*n*-butyl phthalate, benzo[*b*]fluoranthene, and chrysene; and between 1 and 100 ppm, tributyl phosphate, anthracene, phenanthrene, pyrene, benzo[*a*]pyrene, benzo[*a*]anthracene, benzo[*ghi*]perylene, indeno(1,2,3-*cd*)pyrene, naphthalene, acenaphthene, dibenzofuran, fluorene, methanol, ethanol, *n*-butanol, methylene chloride, 4-methyl-2-pentanone, methyl ethyl ketone, acetone, styrene, xylene, and PCBs (<50 ppm). Trichloroethene (TCE) and perchloroethene (PCE) are present in a few tanks in the tenths of a part per million range.

Radionuclides. Beta-gamma emitters in the waste include ^{134}Cs , ^{137}Cs , ^3H , ^{60}Co , ^{90}Sr , ^{14}C , ^{153}Eu , ^{154}Eu , and ^{155}Eu . Alpha emitters present are ^{233}U , ^{238}U , ^{238}Pu , ^{239}Pu , ^{244}Cm , ^{252}Cf , ^{232}Th , ^{238}Th , and ^{241}Am . Gross alpha activity levels in the sludge are as high as 6.5×10^5 Bq/g, and gross beta levels are as high as 5.9×10^7 Bq/g.

pH. The measured pH of the waste ranges from 0.2 to 12.7. Tanks W-13, W-14, and W-15, which received waste from the radiochemical processing facility, and tanks TH-1, TH-2, and TH-3, which received waste from the uranium and thorium pilot plant projects, all have pHs of 3 or below. The wastes in most of the other tanks are above pH 9.

Total organic carbon. The total organic carbon (TOC) in the sludges ranges from 28,000 ppm in tank T-2 to 4020 ppm in tank W-5. Most of the sludges have <10,000 ppm TOC. In the liquids, TOCs range from 2 ppm in tank W-6 to 12,600 ppm in tank T-3. Most liquids have <1000 ppm TOC.

Total solids. Total solids in the sludges range from 76 mg/g in tank 7562 to 1200 mg/g (?) in tank W-11. Most of the sludges have total solids below 500 mg/g. Total solids in the liquids range from 0.3 mg/mL in tank W-11 to 170 mg/mL in tank W-7.

1.3 TREATMENT ALTERNATIVES

Solidification/stabilization (S/S) is a widely accepted treatment for inorganic and radioactive wastes, but there is some technical uncertainty and regulatory disagreement about its suitability for the treatment of organic wastes. Solidification agents include cement in combination with pozzolanic additives such as fly ash or blast furnace slag, thermoplastic agents such as bitumens, and thermosetting polymers such as vinyl ester styrene. All of these materials have advantages and disadvantages in relation to different waste streams and disposal scenarios, and the particular details of various wastes may in some cases favor one over the other.

Solidification with cementitious materials is attractive because it offers some assurance of chemical stabilization of many compounds and produces a mechanically stable waste form. The cement itself is inexpensive and widely available, and processing methods are well understood. However, cementitious solidification results in volume increases that lead to increased disposal costs.

Other treatment methods that have the advantage of volume reduction may require subsequent solidification of the residues. For example, radionuclides in aqueous streams are concentrated in ion exchange resins, but the spent resins still require disposal, by solidification or vitrification. Also, incineration is a common treatment for predominantly organic wastes in high concentrations. However, the organic concentrations in this waste are arguably not high enough to preclude solidification, and ash from the incineration process would still require further treatment. Water recycle is not an issue in this case, and furthermore, some problems have been associated with the solidification of ion exchange resins used for radionuclide removal (e.g., see Morgan and Bostick 1992). Given the ultimate need for solidification of the metals and radionuclides, and since water is required by the mixing process, there is no incentive to remove the water from the waste.

1.4 REGULATORY CONSIDERATIONS

Treatment and disposal of hazardous radioactive wastes on DOE sites must comply with EPA regulations and DOE orders. [The Nuclear Regulatory Commission (NRC) has no authority over DOE or its sites, but its regulations are sometimes used as guidelines in DOE orders.] The EPA defines hazardous wastes as those specifically listed in Subpart D of 40 CFR 261, known as listed wastes, or others exhibiting the characteristics of reactivity, corrosivity, ignitability, or toxicity, known as characteristically hazardous wastes. A waste is characteristically hazardous if its toxicity characteristic leaching procedure (TCLP) leachate contains any contaminant listed in Table 1 of 40 CFR 261.24 at levels above those specified for that contaminant in that table. The wastes in the inactive tank system would likely be deemed hazardous by characteristic, since they contain a number of the contaminants that identify characteristically hazardous wastes. These tank wastes are covered by CERCLA, not by the Resource Conservation and Recovery Act (RCRA); therefore, RCRA and land disposal restrictions (LDRs) may not apply depending on how the waste is handled and treated.

The 1984 amendments to RCRA, known as the Hazardous and Solid Waste Amendments, directed the EPA to ban the land disposal of hazardous wastes. The LDRs

subsequently issued by EPA specified certain "best demonstrated available technologies" (BDAT) for treatment of these wastes to destroy, detoxify, or immobilize the hazardous constituent, and allowable TCLP leachate levels for the hazardous constituents in the wastes. The land bans also specify for many organics the total allowable concentrations that may be disposed on the land, even after treatment. For most inorganic wastes, the BDAT is S/S; for most organics, it is thermal destruction. While use of the BDAT is not absolutely required, the treatment that is used must meet the treatment levels specified by the BDAT. There is currently some debate as to whether the applicable regulatory limits for waste forms containing organics are the total concentration limits or the TCLP limits, and whether the TCLP test is a valid test for measuring the leaching of organics (Brown 1992, Spence and Osborne 1991, Wiles and Barth 1992).

The fundamental NRC requirement that low-level radioactive wastes must meet for shallow land burial is that the waste form possess a minimum compressive strength of 60 psi and that the radionuclides in the waste possess a leachability index of 6. In addition, they must retain minimum compressive strength upon exposure to radiation fields of 10^8 rad. Other applicable requirements are contained in the NRC's 10 CFR 61, DOE Order 5820, and EPA's 40 CFR 193. The radioactivity levels of the wastes under consideration place them in the category of low-level wastes.

1.5 PURPOSE OF THIS STUDY

The purpose of this study is to assess the feasibility of solidifying the low-level liquid and sludge wastes in the inactive tank system. This preliminary assessment will be accomplished by conducting a survey of the literature on S/S to identify (1) contaminants known to interfere with cement set or to compromise the strength and integrity of the waste form and (2) contaminants known to be poorly retained in the cement matrix under leaching conditions. The investigation will focus on problems associated with solidification by cementitious materials.

2. REVIEW OF RETARDATION MECHANISMS

2.1 INTRODUCTION

It is important to understand the mechanisms by which certain classes of compounds retard or inhibit cement set in order to identify potential interferants by the presence of the functional groups that may take part in retardation reactions. The terms retardation or inhibition describe mechanisms that slow cement set but do not necessarily decrease the strength of the fully cured product. However, some compounds in large quantities may produce extreme effects that the normal hydration reactions cannot overcome and that decrease the strength of the cured cement.

2.2 RETARDATION MECHANISMS

A considerable amount of research on reaction mechanisms of retarding admixtures has been done over the past 40 years (Hansen 1959, Young 1972, Taplin 1962, Taylor 1990). Many organic and inorganic compounds have been found to have retarding effects, even at low concentrations. For example, addition of 0.1 wt % sucrose can retard cement set by 10 h (Taylor 1990).

Retardation is thought to occur primarily by adsorption of the retarding compounds onto hydration products, principally calcium silicate hydrate, although the aluminate phase consumes a disproportionate share of the retarder (Young 1972, Taylor 1990). Adsorption occurs by hydrogen bonding between hydroxyl groups and oxygen atoms at the cement surface and by chemical bonding between carboxylic acid oxygens and calcium ions at the cement surface. The adsorption of these compounds forms an impervious coating on the C-S-H and inhibits further hydration by impeding transport of water into the cement grain. According to Young, the retarding compound is ultimately removed from solution by being incorporated into the structure of the hydrated cement.

Lea (1970) presents a clearer picture of how the hydration process overcomes the effects of retarders. According to some theories the early coating of calcium aluminate hydrate particles increases the number of particles available for nucleation and increases the speed of crystal growth once all the retarder has been adsorbed. Lea also suggests that retardation effects are overcome when the impermeable coatings that form on the surface of hydration products burst as a result of an increasing osmotic pressure gradient.

Chelation between either carboxyl or hydroxyl oxygens and metal ions on the surface of the hydration product may be an important adsorption mechanism. It has been observed that compounds with oxygen atoms on nearby or adjacent carbons are effective retarders (Taplin 1962), and they may act by complexation. However, complexation of calcium in solution is not an effective retarding mechanism (Young 1972).

Precipitation is one explanation of the mechanism of retardation by some metal ions (Cocke 1990, Thomas et al. 1981). It is thought that insoluble lead hydroxides and sulfates form an impermeable barrier to hydration by precipitation onto cement particles. Other metal salts such as borates may retard set by forming a coating over the cement grains (Taylor

1990). Precipitation is not thought to be a significant mechanism of retardation by organic compounds (Young 1972).

Some retardation effects may be caused by the inhibition of calcium hydroxide crystallization by the adsorption of retarders onto the calcium hydroxide nuclei (Young 1972). This leads to a larger number of nuclei and to accelerated growth once the solution becomes supersaturated enough with calcium hydroxide for crystal growth to continue.

The mechanisms reviewed above are ways in which compounds may retard the set, but unless large amounts of retarder (>1%) are added, the cement eventually hydrates to a degree sufficient to achieve normal strength (Young 1972). Oily compounds in large concentrations, however, can completely inhibit cement set by covering grains with a hydrophobic coating that effectively prevents hydration.

2.3 POSSIBLE RETARDERS IN THE WASTE

The wastes under consideration in this study contain compounds possessing functional groups known to take part in retardation reactions. In particular, methyl, ethyl, and butyl alcohols; acetone and methyl ethyl ketone; and benzoic acid are among the organics containing hydroxyl groups or carboxyl oxygens. Furthermore, the phthalates are likely to hydrolyze to a carboxylate and an alcohol under alkaline conditions (Caldwell et al. 1990). However, these compounds are present in the wastes in small quantities. Lead is present in greater quantities. It is important to remember that these compounds only retard the set, unless they are present in overwhelming amounts. However, one of the tanks has an oily layer on top of the aqueous layer and another has an organic layer, both of which could present a more serious problem.

3. INORGANIC INTERACTIONS WITH CEMENT

3.1 INTRODUCTION

Inorganic constituents of wastes undergo considerable chemical interaction with cements and pozzolans. Metals in these highly alkaline environments may be precipitated as hydroxides, sulfides, silicates, carbonates, or phosphates. Metals may also sorb onto the mineral phases of cement, clays, fly ash, activated carbon, and zeolites. Other chemical reactions such as complexation affect the behavior of metals by making them unavailable for precipitation reactions. Cement, cement and fly ash mixtures, and cement and silicate mixtures are all effective at chemically stabilizing metal wastes and have been used extensively for this purpose (Conner 1990).

The questions of where in the cement the contaminant exists and in what form are important ones. Whether the contaminant is present on the surface of the hydrated cement crystals or inside the matrix, and whether it is likely to be present as a soluble or an insoluble species both have a bearing on its effect on cement set and on its ability to be retained within the cement solid.

Physical, molecular, and surface characterization tools make possible the determination of where and in what form a contaminant may exist. Electron microscopic methods are the primary methods for physical characterization of cements and visual characterization of cement compounds. Fourier transform infrared spectroscopy (FTIR) provides information about molecular structure by comparing infrared spectra of samples of solidified wastes with reference spectra for expected compounds. The vibrational shifts indicate changes in molecular form that may occur as the result of the added waste. Nuclear magnetic resonance spectroscopy (NMR) is also a useful molecular characterization tool. Surface techniques include X-ray photoelectron spectroscopy (XPS), energy dispersive spectroscopy (EDS) and others. These methods record the characteristic spectra of ions or electrons ejected from the sample surfaces upon bombardment by X rays, electron beams, or ions. This makes possible identification of elements and their oxidation states.

Leaching studies are performed to assess the mobility of the hazardous inorganic constituent in the waste. Leach results can sometimes be correlated with observed microscopic or macroscopic properties of the cement.

3.2 CHEMICAL SPECIATION OF METALS

Lead has been found by FTIR and XPS studies to be present as insoluble lead sulfate or lead carbonate on the interior surfaces of the cement (Ortego et al. 1989, Cocke et al. 1989). XPS studies reveal that mercury probably exists as the fairly soluble mercuric oxide sorbed to the cement surface (Cocke 1990, McWhinney et al. 1990b). Zinc may exist in crystalline form as calcium zincate or as zinc hydroxide (Clark et al. 1985). XPS and FTIR results support the theory that barium exists in insoluble form as barium sulfate or barium carbonate (Cocke 1990, McWhinney et al. 1990a). Barium sulfate in particular has a very large formation constant and very low solubility. Chromium is most stable in aqueous solutions in the Cr(III) and Cr(IV) states, which probably form chromites in the highly alkaline cement

environment. Chromium is thought to be present throughout the matrix of the hydrated cement (Cocke 1990, Ortego et al. 1989). Cadmium may exist in insoluble form as cadmium hydroxide and may accelerate set slightly by providing nucleation sites for the precipitation of calcium hydroxide and calcium silicate hydrate (Cartledge 1990).

3.3 EFFECTS OF METALS ON CEMENT HYDRATION

3.3.1 Lead

Lead retards cement hydration by precipitating onto the surface of the calcium and aluminum silicates as insoluble lead sulfates and carbonates (Thomas et al. 1981, Cocke et al. 1989, Cartledge 1990). These precipitates are thought to form an impermeable coating that acts as a barrier to the diffusion of water. Cartledge et al. (1990) suggested that the lead compounds alternately dissolve and reprecipitate as the pore water pH fluctuates during cure and are ultimately left on the cement surface and available for leaching. Tashiro et al. (1979) and Alford et al. (1981) confirmed that lead retards cement set and that high concentrations (e.g., >5%) lead to a weakened paste. However, Cullinane et al. (1987) found no weakening of the cement paste at lead concentrations as high as 8% and showed that it may even enhance the strength of the final product. However, they found that lead markedly decreases the strength of cement and fly ash mixtures and lime and fly ash mixtures containing as little as 2% lead.

FTIR studies show decreased polymerization for the silicates in the interior of the cement matrix in the presence of lead, while XPS studies show enhanced polymerization of the surface silicates. According to Cocke (1990), the cement grains coated with insoluble lead species are in contact with the supersaturated pore solution longer than they would be in the absence of lead, and this increased contact time leads to enhanced silicate polymerization on the surface of the cement. Interior silicates, deprived of access to the hydrating solution, are less polymerized.

3.3.2 Zinc

Zinc has also been shown to retard cement hydration, but probably by a mechanism different from that of lead (Tashiro et al. 1977, Ortego 1989). Ortego et al. found that the FTIR spectra of zinc/cement samples at high zinc concentrations (>20%) resemble the spectra of dry cement clinker. At these levels, zinc effectively prevents appreciable hydration of the cement, possibly by a chemical, rather than physical, mechanism. Results by Cullinane et al. (1987) show that zinc decreases the strength of cement at ratios above 5%, and decreases strength of cement/fly ash and lime/fly ash samples at ratios as low as 2%.

Zinc has been found to increase the permeability of cement, probably by promoting ettringite formation (Poon et al. 1985, 1986). The increased permeability does not lead to a corresponding increase in zinc concentration in leachates, suggesting that zinc is retained in the matrix by a primarily chemical mechanism.

3.3.3 Mercury

No studies link mercury to retardation of cement set, but it has been associated with increased calcium carbonate formation via conversion of calcium hydroxide to calcium carbonate upon exposure to atmospheric carbon dioxide. The increased calcium carbonate may weaken the cement structure (Cocke 1990, McWhinney et al. 1990b). The calcium-rich formations near mercury in cured cement appear to contain less silicate.

Mercuric oxide is fairly soluble at 10^{-3} to 10^{-4} M and is either sorbed on the surface of the cement matrix or dissolved in the pore solution (Ortego et al. 1989, Poon et al. 1985).

Presence of phenol has been found to lead to increased mercury leaching in wastes solidified with cement, cement/fly ash, and lime/fly ash (Jones et al. 1992).

3.3.4 Others

Zinc, cadmium, and chromium have been associated with increased formation of ettringite (Tashiro et al. 1979, Poon et al. 1986, Campbell et al. 1987). Ettringite is a calcium sulfoaluminate compound that may under some circumstances cause expansion and cracking of the cement and lead to increased leaching of physically bound waste constituents. Campbell et al. found that ettringite formation in a cadmium-containing cement paste exposed to a synthetic seawater leachant caused cracking and led to increased cadmium leaching.

Borates retard hydration, possibly by a precipitation mechanism.

3.4 EFFECTS OF ANIONS

Sulfate in a waste or in water in contact with the solidified waste can react with cement hydrates to form ettringite. Intrusion of chloride ions makes the cement more susceptible to sulfate attack in the disposal environment by dissolving calcium hydroxide and thereby creating a more porous structure (Campbell et al. 1987).

Fluoride forms low-solubility compounds with calcium and would probably not be highly susceptible to leaching (Conner 1990). High nitrate wastes might require dilution to minimize leaching.

3.5 CONCLUSIONS

The retarding effects of lead can be circumvented by limiting the concentration of lead in the mix. Leaching of mercury can be controlled by adjusting the mix parameters to decrease the porosity of the cement or by adding sulfide to precipitate HgS (Conner 1990). Sulfate and cadmium loading should be limited to reduce ettringite formation.

4. ORGANIC INTERACTIONS WITH CEMENT

4.1 INTRODUCTION

The solidification of wastes containing organics presents some problems (U.S. Army 1979, Tittlebaum 1985). Some organics retard or interfere with the set by mechanisms described earlier, and others have been reported to increase the porosity of the cement (Walsh et al. 1986). Some of these problems may be circumvented by oxidation of the organics or by mixing with clays or other calcium- or silica-based admixtures. Another concern aside from the problems associated with cement set is that, in general, organic waste constituents do not form the strong chemical bonds within the cement that some inorganics do. They are therefore not chemically bound in the waste, and their retention is strongly dependent upon physical entrapment. Thus they might be expected to leach entirely from the solidified waste form eventually. Nonpolar hydrophobic compounds having low solubility in water, like PCBs and many polynuclear aromatics, are in general less leachable than polar compounds (Conner 1990).

Many of the same tools used to assess chemical interactions between inorganics and cement are useful in studying the interactions of organics as well. In addition, X-ray diffraction is used for compound identification. Chemical shifts measured by FTIR are useful for indicating the strength of the bonds between organics and cement. Thermogravimetric analysis (TGA) provides information about strength of bonds by measuring the energy required to decompose or desorb compounds. Gas chromatography and mass spectroscopy (GC-MS) can be used to confirm that compounds have decomposed to smaller fragments.

Leach tests can provide information about the mobility of waste constituents, but results for organic wastes may be dependent upon the leachant used. Organics that are not strongly chemically bound may nevertheless not be very susceptible to transport by an aqueous leachant. Thus the TCLP may not be a good measure of chemical immobilization, even though it may provide some indication of how an immobilized organic waste would behave under worst-case environmental conditions.

The decision of whether to use S/S for a waste containing organics depends on the concentration and characteristics of the organics in the waste and on the characteristics of other components of the waste. Wiles and Barth (1992) developed a decision tree for determining whether to use S/S for organics. They elaborated approaches for determining maximum amounts of organics acceptable for treatment by S/S and for determining acceptability of S/S for a particular waste. The decision tree branches are based on concentration limits; whether the waste is mixed or strictly organic; if organic, whether volatile or semivolatile; and if volatile or semivolatile, whether there are suitable S/S processes for such wastes. Their determination of maximum acceptable concentrations for organics to be treatable by S/S is based on (1) a risk analysis procedure and (2) a total waste analysis procedure. The difficulty with these approaches is the uncertainty involved in (1) determining the highest concentration that would not pose an unacceptable risk and (2) knowing what procedure is acceptable for determining total concentrations in the waste.

4.2 ANALYTICAL PROBLEMS

Assessing whether S/S treatment has successfully immobilized organics can be problematic. As mentioned earlier, the TCLP may not provide an accurate measure of immobilization since the organics may not be miscible with water. Some studies of S/S of organics have dealt with wastes having low initial concentrations of organics. Given the detection limits for the analytical procedures, it is very difficult to determine to what extent the organic has been retained in the cement matrix. Some studies have been performed on spiked samples to give a better indication of the degree of retention.

It is particularly difficult to quantify the degree of effectiveness of S/S of volatile organic compounds (VOCs) since a significant fraction of the VOCs may be lost during mixing and curing. Spence et al. (1992) designed their experiment on VOCs to minimize these losses; nevertheless, 10–50% of the VOC was lost during mixing. Weitzman's experiments, designed to facilitate volatilization losses, showed that 80–90% of the VOCs were lost during mixing and curing (Weitzman et al. 1988).

4.3 SOLIDIFICATION/STABILIZATION OF ORGANICS WITH CEMENTITIOUS BINDERS

Numerous studies have been carried out on S/S of organics by cement-based binders, often used in conjunction with pozzolanic additives. This work includes leaching studies to assess treatment of volatile organics, microstructural studies to determine the effects of semivolatile organics on cement structure, and physical tests to determine the durability of the treated wastes.

Jones et al. (1992) and Cullinane et al. (1987) studied the effects of several organic and inorganic compounds on the strength and the leaching characteristics of a solidified/stabilized synthetic metal finishing waste. Spence et al. (1992) and Kolvits and Bishop (1989) carried out leaching studies on solidified volatile organics. McVay et al. (1989) reported success in solidifying a radioactive waste containing organic decontamination agents with a mixture of cement, calcium nitrate, and sodium silicate. Mrochek et al. (1987) used sodium and calcium silicates in a grout formulation for a waste containing organic compounds. Caldwell et al. (1990) studied fly ash, bentonite, and soluble silicates as additives for immobilizing trace organics. Walsh et al. (1986) and Chou et al. (1988) performed microstructural studies on cement mixed with *p*-bromophenol and ethylene glycol. Skipper et al. (1987) investigated the effect of *p*-chlorophenol on cement microstructure. Montgomery et al. (1991a) studied the effects of 3-chlorophenol and chloronaphthalene on cement hydration.

Several site demonstrations document that S/S has been used successfully for stabilization of organics at Superfund sites. Solidtech used a cement-based binder on a waste containing PCBs, heavy metals, oil, and grease at the Imperial Oil/Champion Superfund site in New Jersey (Grube 1989). International Waste Technologies (IWT) solidified PCBs, volatile organics, and heavy metals at the General Electric service shop site in Florida with a cementitious binder and additive (Stinson and Sawyer 1989). [Brown et al. (1992) identify the IWT additive as an organo-clay compound.] The Hazcon process was used to solidify oily wastes in a field demonstration at a Douglassville, Pennsylvania, Superfund site and in a

laboratory study carried out by Waterways Experiment Station to evaluate its potential for use at Rocky Mountain Arsenal in Denver (Myers and Zappi 1987, Sawyer 1989).

4.3.1 Physical Properties of Waste Forms

Solidtech's waste forms containing PCBs and oils possessed high compressive strength and permeabilities of 1×10^{-8} cm/s. Results for physical tests performed for the IWT demonstration on VOCs and heavy metals were satisfactory except for freeze-thaw tests. According to the review by Spence and Osborne (1991), the Hazcon process overcomes the tendency of oils to interfere with the cement set but does not enhance retention of the organics.

Cullinane et al. studied the effects of ten interferants on strength of a solidified synthetic metal finishing waste. The interfering compounds were three heavy metals, five organic compounds, sodium hydroxide, and sodium sulfate. The organics were grease, oil, TCE, hexachlorobenzene, and phenol. The binders used were cement, cement/fly ash, and lime/fly ash. The authors measured unconfined compressive strength at three different interferant:binder ratios: 0.02, 0.05, and 0.08. They found that oil and grease decreased strength at all ratios in all binders. TCE had little effect on cement samples, decreased the strength of the cement/fly ash samples, and increased the strength of the lime/fly ash samples. Hexachlorobenzene had little effect on any samples, only a minor decrease for cement/fly ash and a minor increase for lime/fly ash and for cement at the highest ratio. Phenol decreased strength at all ratios in all binders.

Decontamination wastes containing oxalate, tartrate, citrate, nitrates, and borate were found by McVay et al. to seriously interfere with cement set. Oxalate, tartrate, and citrate are known to bind the calcium ion. Successful solidification was accomplished by using a mixture of cement, calcium nitrate, and sodium silicate. Waste forms possessed compressive strengths of 750 psi, well above the 60-psi NRC requirement.

The Mrochek study tested various sodium and calcium silicate blends on organic wastes containing about 4600 ppm total organic carbon including 24 ppm phenol. Their solidified samples achieved compressive strengths between 500 and 2000 psi depending upon the proportion of silicate used. The study showed that generally, the higher the proportion of silicate, the stronger the samples.

4.3.2 Leaching Properties of Waste Forms

TCLP extracts of the Solidtech samples contained at most 2 ppb lead and 60 ppb chromium. Lead concentrations in the untreated waste ranged from 250 ppb to 520 ppb, and chromium concentrations in the untreated waste were 30 ppb. PCBs were undetectable, but total PCB concentrations in treated and untreated wastes were not given so it is not possible to draw any conclusions about the degree of immobilization that took place. TCLP leachates of treated soil from the IWT study had PCB concentrations below the 1 ppb level in all cases. PCB concentrations in the untreated soil were <300 ppm in most cases. The highest PCB concentration in the soil was 950 ppm. The maximum PCB concentration in the treated soil was 170 ppm in one sample; all others were <110 ppm.

Leaching studies were carried out by Jones et al. (1992) on the solidified synthetic metal finishing waste containing the metal and organic interferants described above (Cullinane et al. 1987). The Extraction Procedure Toxicity Test was used. They found that leachate pH was the major determinant of metal concentrations in the leachate. Additions of up to 8 wt % of organics had no significant effect on metal concentration in the leachate, with the exception of phenol, which was associated with higher mercury concentrations. Phenol itself was leached at high levels from all samples and had a pronounced effect on the strength and the durability of the solidified product. Aside from phenol, only TCE was found at detectable levels in the leachate.

Spence et al. used four vendor-supplied cementitious grouts to solidify a sludge spiked with eight VOCs. The VOCs were acetone, 1,2-dichloroethene, chloroform, methyl ethyl ketone (MEK), benzene, TCE, chlorobenzene, and PCE. Mass balances on the VOCs were attempted during mixing and curing, and it was estimated that 10–50% of the VOCs were lost to evaporation during the mixing and curing process. TCLP and static leaching tests were then carried out. TCE was the most troublesome compound. Results indicated that two of the grouts would produce a waste form that could meet TCLP limits for all eight compounds based on a waste concentration equal to the site maximum. The other two vendors might have been able to meet TCLP limits for all wastes including TCE if the TCE concentration in the spiked sludge were 33 and 29% of the site maximum, which was 145 mg/kg. The authors estimated a distribution coefficient and a leachability index for each organic contaminant for each grout. The majority of the leach indices were between 7 and 8. Leachability indices for PCE and chlorobenzene were higher, ranging from 7.2 to 9.4. Distribution coefficients indicated strong interactions between the binders and acetone, chloroform and PCE, and weaker but significant interactions between binders and 1,2-dichloroethene, MEK, TCE, benzene, and chlorobenzene.

Bishop and Kolvites used a leaching apparatus designed to collect vapors to perform column leach tests on cement pastes containing phenol and TCE. TCE losses from volatilization occurred before and during leaching, making quantification of the results impossible. However, gas chromatograms of the TCE leachate and vapor showed an unidentified compound that could have been a product of the reaction of TCE with potassium hydroxide in the alkaline cement environment. Almost all of the phenol leached out under the conditions of this experiment, indicating little physical or chemical interaction between the cement and the phenol.

McVay's leach testing results showed that all radionuclides possessed leachability indices >6. Leaching was performed using the ANS 16.1 procedure.

Mrochek et al. found that the addition of 10% liquid sodium silicates produced a waste form that retained >99% of the organics in the waste. However, samples exhibited some surface cracking after removal from the high humidity curing environment. Samples with 5% calcium silicate additives produced similar leaching results without any surface cracking. A static leaching test was used.

Caldwell et al. used several different cement-based binders to study the immobilization of a wide variety of organic priority pollutants including aromatics, halogenated aliphatics and esters, phthalate esters, PCBs, and polynuclear aromatics. Cement/bentonite was found to provide better retention at high contaminant loadings (1 mg/g). Cement/activated carbon was

generally superior to all other binders except for the cement/bentonite at high loading. Cement, cement/fly ash, and cement/soluble silicate were the other binders used. In general, the low-solubility organics were found in lower concentrations in the leachates than were the higher solubility compounds.

Côté et al. (1990) established a method to differentiate the extents to which either physical or chemical mechanisms are responsible for the containment of organics. The work involved calculating a total containment factor for a contaminant from the difference between its leachability index and its diffusivity in pure water. A physical containment factor is defined as the total containment factor of a nonreactive tracer, in this case lithium. The difference between a contaminant's total containment factor and the physical containment factor is its chemical containment factor. Working with several proprietary binders and four organics [acenaphthene, aniline, bis(2-chloroethyl)ether, and phenol], the authors showed that acenaphthene and bis(2-chloroethyl)ether are more effectively contained than aniline or phenol. Further, their results showed that the containment for the former two are primarily chemical and for the latter two, primarily physical. Activated carbon best enhanced chemical containment, and silica fume best enhanced physical containment. Five of the binders were portland cement-based and contained either fly ash, activated carbon, or a mixture of hydrated lime and silica fume.

4.3.3 Microstructural Properties of Waste Forms

Recent work at Louisiana State University has explored the effects of *p*-bromophenol (PBP) and ethylene glycol (EG) on cement microstructure. Walsh et al. (1986) found that the effect of EG on the microstructure was evident at lower concentrations compared to PBP as revealed by scanning electron microscopy (SEM) and X-ray diffraction (XRD) analyses; however, the PBP cement also showed some dissimilarities, including more frequent areas of high porosity. EG has been suspected to affect cement set and its mineral constituents (Tittlebaum et al. 1985). It may substitute for the water of hydration, causing changes in the crystal lattices of hydration products.

Chou et al. (1988) found evidence by XRD analysis of interaction of PBP and EG with calcium silicate hydrate gel to produce a more amorphous product in which aggregates of small grains predominate. Diffuse XRD patterns suggested possible bonding of EG and PBP with calcium hydroxide and magnesium hydroxide. Small anomalous crystals of indeterminate composition were noted.

Skipper et al. (1987) found evidence from SEM and energy dispersive X-ray analysis (EDXA) that parachlorophenol (PCP) may react with the unhydrated clinker phase of cement. Increased PCP concentrations were associated with increased smoothness of the cement samples.

Montgomery et al. (1991a) studied the effects of 3-chlorophenol and chloronaphthalene on cement hydration. The phenol inhibited cement hydration and was associated with increased ettringite formation. SEM and EDS revealed that the 3-chlorophenol formed crystalline compounds containing calcium. The hydrophobic chloronaphthalene had no visible effect upon hydration.

4.4 PRETREATMENT OF ORGANICS WITH ORGANOPHILIC CLAYS

The use of organically modified clays to stabilize organics prior to solidification with cement has received increasing attention in recent years. The ability of clays to interact with organics has been known since the 1930s. This characteristic has been exploited for wool degreasing, color adsorption, and stabilization of metals and other cations in radioactive wastes. The recognition that soils attenuate the movement of pesticides and other toxic organics sparked renewed interest in this area (Warren et al. 1986). The work of Montgomery et al. (1991b), Gibbons and Soundararajan (1989), and Soundararajan et al. (1990) has focused on the use of alkylammonium-substituted clays as adsorbents prior to solidification. In such clays, the metal cations such as calcium and magnesium have been exchanged for alkylammonium groups, which act as cationic surfactants. However, clays are known to weaken cement if present in large amounts (Warren et al. 1986).

4.4.1 Chemical Reaction Mechanisms

Warren et al. (1986) undertook a comprehensive review of interactions between aromatic compounds and clay minerals. Among the chemical mechanisms of interaction are complexation, hydrogen bonding, ion exchange, and oxidations that produce free-radical cations in which the products are stabilized by the clay, which acts as a catalyst for the reaction. These are discussed in more detail here.

Complexation and hydrogen bonding are possible reaction mechanisms between clays and nonpolar molecules. Organic cations substituted into the clay matrix overcome the negative effects of an aqueous environment by making the interlamellar space increasingly hydrophilic. They also increase the distance between the mineral layers, which may facilitate the intercalation of large organics. In addition to hydrophilic interactions which are enhanced by the organic content of the clay, hydrogen bonding may also be important, particularly with phenols. The strength of this interaction is influenced by the degree of substitution on the benzene ring and the electron-donating ability of the substituents. Chlorine substitution, for example, enhances the ability of the phenolic hydroxyl group to bond with hydrogen. Large groups in the ortho position can sterically hinder bonding, however.

Cationic pesticides are adsorbed onto clays by an ion-exchange process. Anions may be adsorbed onto silicate surfaces at low pH but are repelled at higher pHs. Nonpolar compounds may become protonated in acidic media and act as cations, which enhances adsorption. Adsorption of nonpolar compounds has been shown to be a function of their solubility in water.

Warren et al. described the reactions between organics and clays that lead to color changes, which involve formation of a free radical cation as a result of oxidation of the compound by the aluminum or iron in the clay matrix. Other compounds structurally similar to dyes such as asphaltenes and resins may be adsorbed onto clays by a mechanism similar to that involved in the color change reaction.

All of the literature on this subject emphasizes that clay-organic interactions are highly specific (Warren et al. 1986, Sheriff et al. 1989, Montgomery et al. 1991b). Therefore, clay additives need to be chosen with the waste constituents in mind, and a given waste may require more than one clay for optimum stabilization.

4.4.2 Details of Specific Studies

Gibbons and Soundararajan (1989) investigated the use of organophilic clay amendments for stabilizing organics. The substituted quaternary ammonium groups they used were synthesized based on the identification of specific compounds in the waste and were designed to increase the interlamellar space in the clay to 25 Å. The wastes contained naphthalene, phenanthrene, bis-(2-chloro-isopropyl)ether, and benzo[*a*]anthracene. Their FTIR data show evidence of several types of bonding between waste and binder, with bond strength depending on waste material and functional group. Differential scanning calorimetry in conjunction with GC-MS (DSC-GC-MS) shows evidence of chemical decomposition upon evaporation from the waste form. No water was used to prepare their samples for FTIR, DSC-TGA, or DSC-GC-MS analysis. A waste form for leaching studies was prepared with a 50:50 waste binder ratio and water sufficient to create a paste. All contaminants were below detection limits in all TCLP leachates and in all methylene chloride extracts except one (Soundararajan et al. 1990). Soundararajan's claims of chemical bonding are based on the energies (greater than the energy of vaporization) necessary to drive organics out of the matrix as measured by TGA and the breakdown of the phenol to simpler compounds indicated by GC-MS.

Sheriff et al. (1989) investigated the use of alkylammonium-substituted clays and charcoal to promote stabilization of phenol, 3-chlorophenol, and 2,3-dichlorophenol in cement-based waste forms. The clays were bentonite substituted with either trimethylammonium chloride, trimethylphenylammonium chloride, hexadecyltrimethylammonium bromide (HDTMA) and benzyldimethyltetradecylammonium chloride (BDTDA). The clays substituted with the long-chain alkyl groups were the most effective of the clays studied, particularly for the 2,3-dichlorophenol, but overall the charcoal had a higher stabilization factor. Over 6% of the 2,3-dichlorophenol was extracted from the cement/clay-BDTDA samples during leaching and over 19% from the cement/clay-HDTMA. The authors saw some evidence that the quaternary ammonium compounds may be removed from the clays under leaching conditions.

Montgomery et al. (1991b) studied the effect of organics on the cement matrix in the presence and the absence of clay, and they compared the effects of unmodified clays with clays that had been substituted with quaternary ammonium groups. They found that in the absence of clay, 3-chlorophenol inhibited hydration of tricalcium silicate at high doses and caused increased formation of ettringite. However, addition of an organophilic clay circumvents this interference for wastes containing up to 15% organics. The key to the enhanced stabilization by substituted clays is the increase in interlamellar distance that is brought about. The proprietary substituted clay used in the study almost doubled the distance, from 0.99 nm to 1.99 nm. The clay-modified samples all showed increased ettringite formation, the substituted clays no more so than the unsubstituted clays. This study found that the substituted clays with adsorbed 3-chlorophenol and chloronaphthalene had no effect on the hydration of cement, indicating that the contaminants remained adsorbed in the clay during hydration. If the 3-chlorophenol concentration was greater than the adsorption capacity of the clay, cement hydration was inhibited.

4.4.3 Questions Surrounding Use of Organophilic Clays

The studies described above present fundamental information on the behavior of organic contaminants in the presence of organically modified clays. They provide encouraging evidence that these clays chemically bond with the organics and prevent their interference

with the cement hydration process. However, it is important that the quantity of organic that can be adsorbed per unit weight of modified clay be determined experimentally. Tests have been conducted to determine the free swell capacity of numerous modified clays (Evans et al. 1989), but these do not provide a quantitative measure of stabilization potential. Leach testing is also needed to determine the leachability of the stabilized waste.

A recent review (Brown et al. 1992) raised a number of questions regarding interpretation of several studies on the stabilization potential of modified clays. These questions concern the following:

- sorbed contaminant concentrations exceeded land ban limits, and contaminant concentrations in the water phase in contact with the clay exceeded drinking water standards in many of these studies;
- contaminant concentration in the water phase in contact with the clay may have been below instrument detection limits in studies that dealt with smaller contaminant concentrations; and
- contaminant concentrations in the leachate of the solidified sorbed organics may have been below detection limits in studies which dealt with smaller contaminant concentrations.

It is important to recognize that the studies cited in the Brown review are aimed at determining the sorptive capacities of the modified clay and the leachability of the contaminant in the solidified product. The percentage of sorption depends on the amount of clay available for sorption and the amount of contaminant available in the water phase in contact with the clay. Percentage of sorption is the parameter of interest in these studies, not contaminant concentration in the water phase at equilibrium, as that review suggests. Furthermore, it is not valid to draw conclusions about potential leachate concentrations based on the concentration in the water phase in contact with the clay during pretreatment. The cement/clay system is not the same as the water/clay system. Likewise, the total concentration of organic in a cement/clay system is not the same as the total concentration of organic in the clay alone. The questions of how to measure the total concentration and whether or not this amount is within regulatory limits are other issues.

It is true that lack of detection of contaminants does not imply absence of contaminants, and one should be reluctant to draw conclusions about sorption based on experiments using very low contaminant concentrations. This is the rationale for the higher concentrations used in experimental work aimed at determining fundamental information about the degree of contaminant sorption and retention.

Soundararajan (1992) summarized the analytical methods for determining stabilization permanence (strength of bonding) and gave quantitative measures indicative of true stabilization. By these guidelines, an FTIR shift of at least 30 cm^{-1} would be indicative of attractions stronger than Van der Waals forces. Minimum energy increases of 30–50% measured by TGA would be indicative of strong bonding. DSC-GC-MS may be used to confirm that compounds forced from the matrix by heat decompose to smaller fragments. Thirty percent retention of organics under drastic leaching conditions (methylene chloride leachant) would also be indicative of strong bonding according to Soundararajan.

4.5 CONCLUSIONS

It may be possible to circumvent some of the problems that have affected S/S of organics. The use of organically modified clays offers promise as a pretreatment method, provided a suitable quaternary ammonium compound is used and the contaminant concentration does not exceed the adsorption capacity of the clay. In general, longer-chain alkylammonium groups (14–16 carbons) show a preference for more hydrophobic compounds and shorter-chain alkylammonium groups (methyl or phenyl-substituted) for less hydrophobic compounds (Sherrif et al. 1989). These methods may not be suitable for very large contaminant concentrations, but they do appear to enhance binding and minimize organic interference with cement set. The wastes in the ORNL inactive tank system contain phenolic compounds, naphthalene, anthracene, and benzo[*a*]anthracene, all of which were subjects of the studies previously described. In view of the results cited above and the relatively low concentrations of these contaminants in these wastes, use of an organically modified clay might be worthy of consideration.

Emulsification has reportedly been used successfully to circumvent the interference caused by oils in mixed wastes (Rosenstiel and Lange 1984, Jones et al. 1986). This approach might be necessary for the wastes in the two tanks containing oily layers.

5. MIXED WASTE INTERACTIONS WITH CEMENT

5.1 INTRODUCTION

Solidification has long been used as a means of containing the radiation produced by radioactive wastes and attenuating the release of radioactive elements to the environment. It also aims to produce a mechanically stable waste form that resists deterioration and makes the disposal site less susceptible to water infiltration. Cement has the longest history of use in the field of radioactive waste disposal, but bitumens, polymers, and gypsum are now also widely employed. Blast furnace slag has been found to enhance retention of many radionuclides in cementitious waste forms.

The low cost of materials and the simplicity of processing are two advantages of using cement as a solidifying agent. The main disadvantages are that the hydration process is susceptible to interferences from chemicals commonly found in radioactive waste streams and that some radionuclides are not well retained by the cement matrix. However, blast furnace slag can enhance the ability of cement to retain many nuclides, even very mobile ones like ^{99}Tc .

5.2 PROBLEMS WITH SOLIDIFICATION OF MIXED WASTES

Borates, highly concentrated sulfate solutions, oils, and chelating agents used in decontamination processes present problems for the cementitious solidification of mixed wastes. Chelating agents, borates, and high concentrations of sulfates retard the hydration process. Chelating agents may also increase the mobility of some radionuclides (Toste 1987). Sulfates and oils create other problems discussed earlier. Also, hydrogen and oxygen gases may be produced from the radiolysis of water within solidified radioactive waste forms.

Some radionuclides are not as well retained in the cement matrix as others. Cowgill (1991) reviewed the literature on the solidification of low-level radioactive wastes and summarized the diffusion coefficients and the leachability indices compiled by Sullivan and Suen (1989). Cesium-137 is the most mobile, with leachability indices ranging from 6.0 to 10.6. Indices for ^{90}Sr range from 7.0 to 10.7. Tritium is also quite mobile, with indices ranging from 7.4 to 9.0.

5.3 SOLUTIONS TO MIXED WASTE SOLIDIFICATION PROBLEMS

5.3.1 Hydration Effects

The high alkalinity of lime in, for example, commercially available masonry cement has been found to overcome the inhibiting effects of boric acid on cement (Staehr and Carlson 1984, Zhou and Colombo 1984). However, the compressive strength of waste forms containing 5–15% borates was found to range from 18 to 50% of normal compressive strength of masonry cement at the same water:cement ratio (Zhou and Colombo 1984).

Sodium sulfate at concentrations $>7\%$ was found to cause catastrophic failure of masonry cement samples subjected to immersion in water. However, plain cement appears to be able to accommodate 9% sodium sulfate with no ill effect (Zhou and Colombo 1984). Atabek et al. (1990) found that blends of cement and silicate were more resistant to sulfate and chloride attack than plain cements, possibly because of their fine pore network and low portlandite content.

Jones et al. (1986) described emulsifying contaminated oils prior to solidification with a cement/lime binder. Rosenstiel and Lenz (1984) also described the successful use of an emulsifier with gypsum cement for the solidification of mixed organic wastes that included lubrication oils, chelating agents, solvents, paint thinners, acetone, hydraulic fluids, and turbine oils. Problems were reported with wastes containing alcohol solvents exceeding concentrations of 25% (presumably by weight) and with (unspecified) high concentrations of acetone and paint thinners. These problems were circumvented by diluting the wastes.

5.3.2 Radionuclide Retention

Natural zeolites and clays such as anielitic clays, attapulgite, and bentonite are widely reported to attenuate cesium movement (Staehr and Carlson 1984, Moore et al. 1982, McDaniel et al. 1988). McDaniel found that attapulgite is effective in smaller quantities than other clays without increasing the volume of free-standing water. Bentonite is also effective for retarding cesium migration, but not in salt solutions. Torstenfeldt and Hedin (1988) found that 5 wt % zeolites decreased diffusivity of cesium by 2 orders of magnitude, from 10^{-10} to 10^{-12} (m^2/s). Leaching rates were decreased by an order of magnitude, from 10^{-7} to 10^{-8} ($\text{kg}/\text{m}^2\text{-s}$). Atkinson and Nickerson (1988) found that cesium sorption is dependent on liquid:solid ratio, unlike some other nuclides. Andersson et al. (1981) measured the diffusivity of cesium to be 10^{-14} on the average for pure cement and cement/blast furnace slag. They found that cesium sorbed much more strongly to the cement/slag mix. Assuming a diffusivity of 10^{-13} m^2/s , they estimated that a solution separated from a cesium solution by a concrete wall 0.4 m thick would reach a concentration equal to 1% of the cesium concentration on the other side in 3900 years. Atabek et al. (1990) found that a cement/silicate blend decreased cesium leaching.

Strontium leaching has been linked to the leach rate of calcium and to the amount of free lime (CaO) in the cement matrix. Furthermore, the leaching of both calcium and strontium is reduced by addition of fly ash (McDaniel et al. 1988, Moore et al. 1982). Cement/silicate blends enhanced retention of strontium, possibly because of their low portlandite content, low Ca:Si ratio, and fine pore network. Phosphate appears to enhance strontium retention; however, phosphate is also listed among retarders of cement (Atabek et al. 1990).

Smith and Walton (1990) investigated the effects of carbonation on the attenuation of release of ^{90}Sr and ^{60}Co from concrete. Virtually all of the portlandite and possibly some of the calcium silicate hydrate is available for the formation of calcium carbonate (calcite) via incorporation of carbon dioxide or carbonic acid. This reaction forms a carbonated shell on the external surfaces of concrete exposed to carbon dioxide or carbonic acid in the soil. As a result, divalent radionuclides migrating through the cement may substitute for the calcium to form a solid solution. This decreases the rate of release of the radionuclide from the cement. Release rates for ^{90}Sr and ^{60}Co were estimated by the authors to be 5 orders of

magnitude less. Formation of solid solutions of radionuclides in calcite might be enhanced by using limestone aggregate in the mix.

The formation of C-S-H phases that incorporate uranium may limit the mobility of uranium in cement. Uranium(VI) at concentrations above $10^{-7} M$ reacts with cement hydrates to form uranophane. At lower concentrations, uranium is more likely to be immobilized by sorption (Atkins et al. 1989).

5.3.3 Radiolytic Gas Production

Hydrogen and oxygen gases may form from the radiolysis of water inside solidified wastes. So-called FUETAP concrete (formed under elevated temperature and pressure) reportedly produces only 5% as much of these gases as normal concrete (Moore et al. 1982). Gas production is not a widely reported problem with low-level radioactive waste forms, however.

5.4 CONCLUSIONS

The addition of some combination of clay, blast furnace slag, or fly ash could be considered to decrease leaching of radionuclides. The boron concentrations in the waste are below detection limits, so a high-lime mixture is not called for. Crushed calcite might be added to act as a sink for divalent radionuclides.

6. PRELIMINARY EXPERIMENTAL DESIGN

Based on the characterization data available during this study, no insurmountable problems are foreseen in solidifying the tank wastes. The biggest concern identified was the high levels of lead or sulfate in some of the tanks, usually in the tank sludge, implying some insoluble lead or sulfate. Table 1 lists these potentially high concentrations and the tanks involved. From Table 1, apparently none of the tank wastes have lead concentrations as high as 5 wt %, implying that lead will not present a problem to solidification. Apparently Analytical Services was unable to determine with accuracy the sulfate concentration in the soft sludge for tanks T-3 and T-4. Thus, the sulfate is reported as less than some high weight percentage. The high sulfate contents are only part of the tank contents. The other tank contents plus the formulation ingredients will dilute these sulfate concentrations. The limit of 5 wt % applies to the final solidified waste form. To maintain a restriction of <5 wt % sulfate in the waste form, the soft sludge in tank W-7 must be <75 wt % of the waste form, the soft sludge in tank T-2 must be <36 wt % of the waste form, the high sulfate liquid in tank T-9 must be <74 wt % of the waste form, and the high sulfate liquid in tank TH-4 must be <60 wt % of the waste form. The other high sulfate liquid sample and the soft sludge sample from tank TH-4 were already measured as <5 wt % and require no dilution. Waste is usually diluted even more, since waste loadings are rarely as high as 60 wt % in cementitious waste forms.

Table 1. High lead or sulfate concentrations as reported in the waste characterization report (ORNL 1992)

Tank	Lead (wt %)	Sulfate (wt %)
W-7 (soft sludge)	0.03	6.7
W-11 (hard sludge)	1.4	*
T-2 (soft sludge)	0.035	14
T-3 (soft sludge)	0.03	<62.5
T-4 (soft sludge)	0.051	<42
T-9 (liquid)	0.054	6.8
TH-4 (liquid)	<0.0002	8.3
(liquid)	<0.0005	1.4
(soft sludge)	0.0038	4.8

Only the unknown sulfate concentrations for the soft sludges of tanks T-3 and T-4 may require extensive dilutions. If the concentrations were truly as high as the values listed in Table 1, then the soft sludge of tank T-3 and the soft sludge of T-4 could be no more than 8 wt % and 12 wt %, respectively, of the waste forms for these two tanks. Such low waste

loadings can lead to large volume increases, but it is more likely that these tanks contain sulfate concentrations closer to those measured for the other tanks and that waste loadings as high as 50 wt % can be allowed. Most cementitious waste forms have waste loadings of 20-50 wt %.

It is recommended that a baseline formulation be developed that can be tested with the contents of each tank. The baseline formulation would be developed for a reference waste. This reference waste may be any one of several options agreed to by the sponsor and the developer but should be representative of the tank wastes. The most likely options are (1) a composite from all of the tanks, (2) a surrogate incorporating the worst collective features of the tank wastes, and (3) the wastes from one tank selected to represent all of the tanks. Regardless of the source of the reference waste, it is recommended that a mixture experiment be conducted to develop a baseline formulation for the reference waste. It must be emphasized that the baseline formulation cannot be guaranteed to work for the wastes from every tank; wastes from each tank must be tested individually with the formulation, unless all tank contents are homogenized. The baseline formulation approach avoids a mixture experiment for each tank, but modifications may have to be made for individual tanks (because of differences in pH, total solids, etc. in the tank wastes). A mixture experiment that included the waste composition as variables could be conducted, but because the number of possible waste components is large, the number of tests required would be large and each tank's contents would still have to be tested.

The final experimental design for the baseline formulation is not presented in this report, but the preliminary steps are. First, the ingredients of the cementitious waste form must be selected. Water is necessary for hydrating the solidifying agents and for fluidizing the dry solids for processing purposes. Some water is in the tank wastes, but the tank wastes vary from liquid solutions to sludges. The sludges may require additional water in the formulation. For this reason the waste is divided into two parts: oven-dried solids and water. Thus, the first variable is the oven-dried solids and the second variable is the water, which is the combination of the water from the waste plus added water. The third variable is one of the better solidifying agents, ground granulated blast furnace slag (slag). Slag requires activation, so the fourth variable is a cement to activate the slag. Heat evolution can be a problem in some S/S applications, especially for large monoliths, so Type II-LA (moderate heat of hydration) Portland cement is recommended, though other cements can activate the slag. Class F fly ash is added as the fifth variable, although it may not be needed for this application. The remaining variables are any specialty additives that may be required to control water bleeding or contaminant release. The sludges may not require a clay to control water release, but attapulgite was added as the sixth variable since both liquid and sludge wastes are in the tanks. Illite for ^{137}Cs and an organophilic clay for the organics make variables seven and eight. Other variables such as calcium silicate or sodium silicate could be added for other contaminants, plus different organophilic clays may be needed for different organics. Any additive that may be used for a given contaminant should be included in the mixture experiment design if that contaminant is present in a sufficient concentration in the reference waste. The mixture experiment design will test the performance with and without this additive, as long as part of the performance testing includes the effectiveness of immobilizing this contaminant. Because this design is preliminary, careful discussions with the sponsor should establish the formulation objectives and the selection of the reference waste and the variables.

The advantage of the mixture experiment is that it will generate empirical predictive models for the properties tested during the mixture experiment. This not only allows recommendation of formulations but quantitative estimates of the effect on properties of changes in composition. It is important to include all of the possible variables and the entire constrained region of interest in the original mixture experiment. Table 2 defines a preliminary list of potential variables. The basic matrix will be slag/cement. An important part of the mixture experiment will be to explore the region where only slag and cement are added to the waste and water. Once all of the potential ingredients and their constraints have been identified, a mixture experiment design will be generated for the reference waste, the mixture experiment conducted, surface response models generated, validation tests performed if needed, and formulations recommended for the reference waste. A baseline formulation will be selected in conjunction with the sponsor and tested. This formulation must be tested with wastes from each tank, unless the wastes are mixed. The baseline formulation may not be optimal for each tank but may be satisfactory. If it is satisfactory, no further development is required. If it is not satisfactory for a given tank, then modifications will have to be made for that tank.

Table 2. Preliminary list of variables for the tank wastes grout formulation

Ingredient	Mass fraction	Ratio with waste solids (X_i/X_0)
Waste solids	X_0	N/A
Water	X_1	W_1
Slag	X_2	W_2
Cement	X_3	W_3
Fly ash	X_4	W_4
Attapulgate	X_5	W_5
Illite	X_6	W_6
Organo clay 1	X_7	W_7
Organo clay 2	X_8	W_8
Additive for ^3H	X_9	W_9

The minimum number of tests required for the ten variables listed in Table 2 would be 10 for a first-order model and 65 for a second-order model. A second-order model is recommended, and more than the minimum number of tests should be run in order to test replicates, test centroids, and calculate standard deviations. Ten extra tests are sufficient, but another ten, to give a total of 85 tests, would yield an extra degree of certainty. This number depends on the number of ingredients finally selected. The properties of interest should be measured for each test. Statisticians and a statistical program will be used to identify the

vertices, edge midpoints, face centroids, and volume centroid of the constrained region and to select the points for testing.

7. SUMMARY AND CONCLUSIONS

The inorganic constituents of the waste pose no insurmountable obstacle to solidification with a cement-based binder. Potential interferences from the tanks identified thus far (tanks W-7, W-11, T-2, T-3, T-4, T-9, and TH-4) containing lead or sulfate in high concentrations can be controlled by limiting the quantity of interferant solidified per unit weight of binder to <5%.

The combined organic concentration in even the most concentrated tanks would not likely cause significant interference with cement set. For example, tank W-11, with a combined organic concentration of ~900 mg/L at a waste:binder ratio of 0.5 would represent <0.05 wt % of the waste form. It is also likely that the leaching of the toxicity characteristic contaminants from the solidified wastes would be under the TCLP limit. For example, in tank W-10, the measured concentrations of all but one of the VOCs is under the TCLP limit. The one compound that is not under the limit (TCE) would be under the limit after the twentyfold dilution the TCLP entails.

Organically modified clays could be considered as an additive to enhance retention of the organic contaminants. The scope of any screening test to determine sorption capacities of clays for specific contaminant compounds would be very large in light of the number of compounds in the waste. A general approach would be to look at the capacities in the literature—for example, 0.51 g of 3-chlorophenol per gram of clay, and 0.65 g chloronaphthalene per gram of clay (representative of polar and hydrophobic compounds)—and use these as general guidelines. Montgomery et al. (1991b) used these proportions and a clay:cement ratio of 0.5 (dry weight basis) with no adverse effect on set.

Emulsification or removal of the oily layers in tanks WC-15 and WC-17 would probably be advisable, even though small volumes are evidently involved. The organic layer containing PCBs in tank WC-17 is less than 6 in. thick. The oily layer resembling 90-weight oil in tank WC-15 is described in the waste characterization report (ORNL 1992) as thin.

The presence of radionuclides warrants the use of some combination of blast furnace slag, fly ash, or clay. Clay is also useful for preventing excessive solids separation in high solids wastes. Another alternative for enhancing radionuclide retention is the use of crushed limestone.

In light of the fact that organic retarders preferentially adsorb onto the aluminate phase of cement without having a major effect on strength via this adsorption, it would be interesting to test whether adding a high-alumina cement to the binder mixture would have the effect of decreasing the inhibiting effects of such compounds.

8. BIBLIOGRAPHY

- Alford, N. M., A. A. Rahman, and N. Salih. 1981. "The Effect of Lead Nitrate on the Physical Properties of Cement Pastes," *Cement Concrete Res.* 11, 235-245.
- Andersson, K., B. Torstenfelt, and B. Allard. 1981. "Diffusion of Cesium in Concrete," *Scientific Basis for Nuclear Waste Management*, Vol. 3, pp. 235-242.
- Atabek, R., P. Bouniol, E. Revertegat, J. Oliver, P. Gegout, and M. Jorda. 1990. "Nuclear Waste Immobilization in Cement-Based Materials: Overview of French Studies," *Scientific Basis for Nuclear Waste Management*, Vol. 176.
- Atkins, M., J. Cowie, F. P. Glasser, T. Japp, A. Kindness, and C. Pinter. 1989. "Assessment of the Performance of Cement-Based Composite Material for Radioactive Waste Immobilization," *Scientific Basis for Nuclear Waste Management*, Vol. 176.
- Atkinson, A., and A. K. Nickerson. 1988. "Diffusion and Sorption of Cesium, Strontium, and Iodine in Water-Saturated Cement," *Nucl. Technol.* 81, 100-113.
- Boyd, S. A., M. M. Mortland, and C. T. Chiou. 1988. "Sorption Characteristics of Organic Compounds on Hexadecyltrimethylammonium-Smectite," *Soil Sci. Soc. Am. J.* 52, 652-657.
- Boyd, S. A., S. Shaobai, J.-F. Lee, and M. M. Mortland. 1988. "Pentachlorophenol Sorption by Organo-Clays," *Clays Clay Miner.* 36(2), 125-130.
- Bricka, R. M., and L. W. Jones. 1990. *An Evaluation of Factors Affecting Solidification/Stabilization of a Heavy Metal Sludge*, Final Report, Interagency Agreement DW930146-01-01 between Environmental Laboratory, Waterways Experiment Station, U.S. Army Corps of Engineers, and Risk Reduction Engineering Laboratory, U.S. Environmental Protection Agency, Cincinnati, Ohio.
- Bricka, R. M., T. Holmes, and M. J. Cullinane. 1987. *An Evaluation of Stabilization/Solidification of Metal Hydroxide Sludge (F006)*, Technical Report EL-88-XX, U.S. Army Corps of Engineers Waterways Experiment Station, Vicksburg, Mississippi.
- Brown, R. E., B. S. Jindal, and J. D. Bulzan. 1992. "A Critical Review of the Effectiveness of Stabilization of Solidification of Hazardous Organic Wastes," in *Solidification and Stabilization of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 43-60.
- Caldwell, R. J., P. L. Côté, and C. C. Chao. 1990. "Investigation of Solidification for the Immobilization of Trace Organic Contaminants," *Hazard. Waste Hazard. Mater.* 7(3), 273-282.
- Campbell, K. M., T. El-Korichi, D. Gress, and P. Bishop. 1987. "Stabilization of Cadmium and Lead in Portland Cement Paste Using a Synthetic Seawater Leachant," *Environ. Prog.* 6(2), 99-103.

- Cartledge, F. K., L. G. Butler, D. Chalasani, H. C. Eaton, F. P. Frey, E. Herrera, M. E. Tittlebaum, and S.-L. Yang. 1990. "Immobilization Mechanisms in Solidification/Stabilization of Cd and Pb Salts Using Portland Cement Fixing Agents," *Environ. Sci. Technol.* 24(6), 867-873.
- Chalasani, D., F. Cartledge, H. C. Eaton, M. E. Tittlebaum, and M. B. Walsh. 1986. *Hazard. Waste Hazard. Mater.* 3(2), 167-173.
- Chou, A. C., H. C. Eaton, F. Cartledge, and M. E. Tittlebaum. 1988. "A Transmission Electron Microscopic Study of Solidified/Stabilized Organics," *Hazard. Waste Hazard. Mater.* 5(2), 145-153.
- Clark, D. E., P. Colombo, and R. M. Neilson. 1982. *Solidification of Oils and Organic Liquids*, BNL-51612, Brookhaven National Laboratory, Upton, New York.
- Cocke, D. L. 1990. "The Binding Chemistry and Leaching Mechanisms of Hazardous Substances in Cementitious Solidification/Stabilization Systems," *Proceedings of the Gulf Coast Hazardous Substances Research Center Conference*, pp. 81-102.
- Cocke, D., J. D. Ortego, H. McWhinney, K. Lee, and S. Shukla. 1989. "A Model for Lead Retardation of Cement Setting," *Cement Concrete Res.* 19(1), 156-159.
- Conner, J. R. 1990. *Chemical Fixation and Solidification of Hazardous Wastes*, Van Nostrand Reinhold, New York.
- Côté, P. L., R. Caldwell, and C. C. Chao. 1990. "Physical and Chemical Containment of Organic Contaminants in Solidified Waste," *Waste Manage.* 10, 95-102.
- Cowgill, M. G. 1991. *A Comparison of Solidification Media for the Stabilization of Low-Level Radioactive Wastes*, BNL-52304, Brookhaven National Laboratory, Upton, New York.
- Cullinane, M. J., R. M. Bricka, and N. R. Francingues, Jr. 1987. "An Assessment of Materials That Interfere With Solidification/Stabilization Processes," *Proceedings of the 13th Annual Research Symposium*, U.S. Environmental Protection Agency, Cincinnati, Ohio, pp. 64-71.
- Evans, J. C., S. E. Tancoski, and G. Alther. 1989. "Organic Waste Treatment with Organically Modified Clays," *Proceedings of the 3rd International Conference on New Frontiers in Hazardous Waste Management*, EPA/600/9-89/072, U.S. Environmental Protection Agency, pp. 48-57.
- Gibbons, J. J., and R. Soundararajan. 1989. "The Nature of Chemical Bonding Between Organic Wastes and Organophilic Binders, Part 2," *Am. Lab.* 21(7), pp. 70-79.
- Gilliam, T. M., R. D. Spence, B. S. Evans-Brown, I. L. Morgan, J. L. Shoemaker, and W. D. Bostick. 1988. "Performance Testing of Blast Furnace Slag for Immobilization of Technetium in Grout," *Spectrum '88: International Topical Meeting on Nuclear and Hazardous Waste Management*, pp. 109-111.

Grube, W. E., Jr. 1989. "Evaluation of the Soliditech Solidification/Stabilization Technology," *Proceedings of the 3rd International Conference on Hazardous Waste Management*, EPA/600/9-89/072, U.S. Environmental Protection Agency, pp. 176-188.

Hansen, W. C. 1959. *Symposium on Effect of Water-Reducing Admixtures and Set-retarding Admixtures on Properties of Concrete*, ASTM STP 266, p. 3-23.

Jones, D., J. Remark, T. F. D'Muhala, and R. C. Ward. 1986. "Solidification of Oil at the James A. Fitzpatrick Nuclear Power Station," *Proceedings from the International Symposium on Alternative Low-Level Waste Technologies*, pp. 311-315.

Jones, L. W. 1988. *Interference Mechanisms in Waste Solidification/Stabilization Processes: Literature Review*, Interim Report: Interagency Agreement DW219306080-01-0 between Waterways Experiment Station, U.S. Army Corps of Engineers, Vicksburg, Mississippi, and Risk Reduction Engineering Laboratory, U.S. Environmental Protection Agency, Cincinnati, Ohio.

Jones, L. W., R. M. Bricka, and M. J. Cullinane, Jr. 1992. "Effects of Selected Waste Constituents on Solidified/Stabilized Waste Leachability," *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 193-203.

Kolvites, B., and P. Bishop. 1989. "Column Leach Testing of Phenol and Trichloroethylene Stabilized/Solidified with Portland Cement," *Environmental Aspects of Stabilization and Solidification of Hazardous and Radioactive Wastes*, ASTM STP 1033, P. Côté and M. Gilliam, Eds., American Society of Testing and Materials, Philadelphia, pp. 238-250.

Lea, F. M. 1970. *Chemistry of Cement and Concrete*, Chemical Publishing Company, New York.

Mattus, A. J., T. M. Gilliam, and L. R. Dole. DATE? *A Review of EPA, DOE, and NRC Regulations Regarding Establishment of Solid Waste Performance Criteria*, ORNL/TM-9322, Oak Ridge National Laboratory, Oak Ridge, Tennessee.

McDaniel, E. W., O. K. Tallent, T. L. Sams, D. B. Delzer, and W. D. Bostick. 1988. "Basis for Selecting Cement-Based Waste Forms for Immobilizing Radioactive Grout," *Scientific Basis for Nuclear Waste Management*, Vol. 127.

McVay, C. W., J. R. Stimmel, and S. Marchetti. 1989. "WVNS Experience with Cement Solidification of Decontaminated Spent Fuel Waste," *Proceedings of Workshop on Cement Stabilization of Low-level Radioactive Waste*, NUREG/CP-0103, Nuclear Regulatory Commission, Washington, D.C.

McWhinney, H. G., M. W. Rowe, D. L. Cocke, J. D. Ortego, and G.-S. Yu. 1990. "X-Ray Photoelectron and FTIR Spectroscopic Investigation of Cement Doped with Barium Nitrate," *J. Environ. Sci. Health A25*(5), 463-477.

McWhinney, H. G., D. L. Cocke, K. Balke, and J. D. Ortego. 1990. "An Investigation of Mercury Solidification and Stabilization in Portland Cement Using X-Ray Photoelectron Spectroscopy and Energy Dispersive Spectroscopy," *Cement Concrete Res.* **20**, 79-91.

Montgomery, D. M., C. J. Sollars, R. Perry, S. E. Tarling, P. Barnes, and E. Henderson. 1991(a). "Treatment of Organic-Contaminated Industrial Wastes Using Cement-Based Stabilization/Solidification—I. Microstructural Analysis of Cement-Organic Interactions," *Waste Manage. Res.* **9**, 103-111.

Montgomery, D. M., C. J. Sollars, R. Perry, S. E. Tarling, P. Barnes, and E. Henderson. 1991(b). "Treatment of Organic-Contaminated Industrial Wastes Using Cement-Based Stabilization/Solidification—II. Microstructural Analysis of the Organophilic Clay as Pre-Solidification Adsorbent," *Waste Manage. Res.* **9**, 113-125.

Moore, J. G., G. C. Rogers, S. Katz, M. T. Morgan, and E. Newman. 1982. "FUETAP Concretes—Tailored Autoclaved Concretes for the Fixation of Radioactive Wastes," *Waste Management '82*, pp. 267-276.

Morgan, I. L., and W. D. Bostick. 1992. "Performance Testing of Grout-Based Waste Forms for the Solidification of Anion Exchange Resins," *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 133-145.

Mrochek, J. E., T. M. Gilliam, and E. W. McDaniel. 1987. "Grout Formulation for the Immobilization of Mixed Organic-Containing Wastes," *Spectrum '86: Proceedings of the American Nuclear Society International Topical Meeting, Waste Management and Decommissioning*, American Nuclear Society, pp. 56-76.

Myers, T. E., and M. E. Zappi. 1987. *Laboratory Investigation of Organic Contaminant Immobilization by Proprietary Processing of Basin F Liquid Rocky Mountain Arsenal, Denver, Colorado*, Technical Report EL-87-11, U.S. Army Waterways Experiment Station, Vicksburg, Mississippi.

Myers, T. E., N. R. Francingues, Jr., D. W. Thompson, and D. O. Hill. 1985. "Sorbent Assisted Solidification," *Proceedings: International Conference on New Frontiers for Hazardous Waste Management*, EPA/600/9-85/025, U.S. Environmental Protection Agency, Cincinnati, Ohio.

Neuwirth, M., R. Mikula, and P. Hannack. 1989. "Comparative Studies of Metal Containment in Solidified Matrices by Scanning and Transmission Electron Microscopy," *Environmental Aspects of Stabilization and Solidification of Hazardous and Radioactive Wastes*, ASTM STP 1033, P. Côté and M. Gilliam, Eds., American Society of Testing and Materials, Philadelphia, pp. 201-213.

ORNL (Oak Ridge National Laboratory). 1992. *Waste Characterization Data Manual for the Inactive Liquid Low-Level Radioactive Waste Tank Systems at Oak Ridge National Laboratory, Oak Ridge, Tennessee*, ORNL/ER-80, Oak Ridge National Laboratory, Oak Ridge, Tennessee.

Ortego, J. D., S. Jackson, G.-S. Yu, H. G. McWhinney, and D. L. Cocke. 1989. "Solidification of Hazardous Substances—a TGA and FTIR Study of Portland Cement Containing Metal Nitrates," *J. Environ. Sci. Health A24*(6), 589–602.

Poon, C. S., C. J. Peters, and R. Perry. 1985. "Mechanisms of Metal Stabilization by Cement Based Fixation Processes," *Sci. Total Environ.* **41**, 55–71.

Poon, C. S., A. I. Clark, and R. Perry. 1986. "Permeability Study on the Cement Based Solidification Process For the Disposal of Hazardous Wastes," *Cement Concrete Res.* **16**, 161–172.

Rosenstiel, T. L., and R. G. Lange. 1984. "The Solidification of Low Level Radioactive Organic Fluids with Envirostone Gypsum Cement," *Waste Management '84*, pp. 169–172.

Sawyer, S. 1989. *Applications Analysis Report: HAZCON Solidification Process*, Douglassville, Pennsylvania, EPA/540/A5-89-001, U.S. Environmental Protection Agency.

Sheriff, T. S., C. J. Sollars, D. Montgomery, and R. Perry. 1987. *Environ. Technol. Lett.* **8**, 501–514.

Sheriff, T. S., C. J. Sollars, D. Montgomery, and R. Perry. 1989. "The Use of Activated Charcoal and Tetra-Alkylammonium-Substituted Clays in Cement-Based Stabilization/Solidification of Phenols and Chlorinated Phenols," *Environmental Aspects of Stabilization and Solidification of Hazardous and Radioactive Wastes*, ASTM STP 1033, P. Côté and M. Gilliam, Eds., American Society of Testing and Materials, Philadelphia, pp. 273–286.

Shively, W., P. Bishop, D. Gress, and T. Brown. 1986. "Leaching Tests of Heavy Metals Stabilized with Portland Cement," *J. Water Pollut. Control Fed.* **58**(3), 235–241.

Skipper, D. G., H. C. Eaton, F. K. Cartledge, and M. E. Tittlebaum. 1987. "Scanning Electron Microscopy/Energy Dispersive X-Ray Analysis of Type I Portland Cement Pastes Containing Parachlorophenol," *Cement Concrete Res.* **17**, 851–863.

Smith, R. W., and J. C. Walton. 1990. "The Effects of Calcite Solid Solution Formation on the Transient Release of Radionuclides from Concrete Barriers," *Scientific Basis of Nuclear Waste Management*, Vol. 212, pp. 403–409.

Soundararajan, R. 1992. "Guidelines for Evaluation of the Performance of a Stabilization/Solidification Technology," *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 33–39.

Soundararajan, R., E. Barth, and J. J. Gibbons. 1990. "Using an Organophilic Clay to Chemically Stabilize Waste Containing Organic Compounds," *Hazard. Mater. Control* **3**(1).

Spence, R. D., and S. C. Osborne. 1991. *Literature Review of Stabilization/Solidification of Volatile Organic Compounds and the Implications for Hanford Grout*, unpublished.

Spence, R. D., T. M. Gilliam, I. L. Morgan, and S. C. Osborne. 1990. *Immobilization of Volatile Organics in Commercial Cement-Based Waste Forms*, ORNL/TM-11251, Oak Ridge National Laboratory, Oak Ridge, Tennessee.

Spence, R. D., T. M. Gilliam, I. L. Morgan, and S. C. Osborne. 1992. "Stabilization/Solidification of Wastes Containing Volatile Organic Compounds in Commercial Cementitious Waste Forms," *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 61-72.

Staehr, J., and J. Carlson. 1984. "Technical Advances in the Use of Cement for Effective Solidification of Low Level Radioactive Waste," *Waste Management '84*, pp. 181-184.

Stinson, M. K., and S. Sawyer. 1989. "In Situ Stabilization/Solidification of PCB-Contaminated Soil," *Proceedings of the 3rd International Conference on New Frontiers in Hazardous Waste Management*, EPA/600/9-89/072, Environmental Protection Agency, pp. 151-160.

Sullivan, T. M., and C. J. Suen. 1989. *Low-Level Waste Shallow Land Disposal Source Term Model: Data Input Guides*, NUREG/CR-5387, Nuclear Regulatory Commission, Washington, D.C.

Taplin, J. H. 1962. Discussion in *Proceedings of the Fourth International Symposium on Chemistry of Cements*, p. 924.

Tashiro, C., H. Takahashi, M. Kanaya, I. Khrakida, and R. Yoshida. 1977. "Hardening Property of Cement Mortar Adding Heavy Metal Compounds and Solubility of Heavy Metals from Hardened Mortar," *Cement Concrete Res.* 7(3), 283-290.

Tashiro, C., J. Oba, and K. Akama. 1979. "The Effects of Several Heavy Metal Oxides on the Formation of Ettringite and the Microstructure of Hardened Ettringite," *Cement Concrete Res.* 9, 303-308.

Taylor, H. F. W. 1990. *Cement Chemistry*, Academic Press, San Diego, California.

Thomas, N. L., D. A. Jameson, and D. D. Double. 1981. "The Effect of Lead Nitrate on the Early Hydration of Portland Cement," *Cement Concrete Res.* 11(1), 143-153.

Tittlebaum, M. E., R. K. Seals, F. K. Cartledge, and S. Engels. 1985. *Crit. Rev. Environ. Control* 15(2), 179-211.

Tittlebaum, M. E., F. K. Cartledge, D. Chalasani, H. Eaton, and M. Walsh. 1985. "A Procedure for Characterizing Interactions of Organic with Cement: Effect of Organics on Solidification/Stabilization," *Proceedings, International Conference on New Frontiers for Hazardous Waste Management*, U.S. Environmental Protection Agency, Washington, D.C.

Torstenfelt, B., and G. Hedin. 1988. "Leaching of Cesium From a Cement Matrix," *Scientific Basis for Nuclear Waste Management*, Vol. 127, 1988, pp. 495-500.

Toste, A. P., R. B. Lucke, T. J. Lechner-Fish, D. J. Hendren, and R. B. Myers. 1987. "Organic Analysis of Mixed Nuclear Wastes," *Waste Management '87*, pp. 323-329.

U.S. Army Waterways Experiment Station, **DATE?** *Survey of Solidification/Stabilization Technology for Hazardous Industrial Wastes*, EPA-600/2-79-056, U.S. Environmental Protection Agency.

Walsh, M. B., H. C. Eaton, M. E. Tittlebaum, F. Cartledge, and D. Chalasani. 1986. "The Effect of Two Organic Compounds on a Portland Cement-Based Stabilization Matrix," *Hazard. Waste Hazard. Mater.* 3(1), 111-123.

Warren, D. S., A. I. Clark, and R. Perry. 1986. "A Review of Clay-Aromatic Interactions with a View to Their Use in Hazardous Waste Disposal," *Sci. Total Environ.* 54, 157-172.

Weitzman, L., L. E. Hamel, and E. Barth. 1988. "Evaluation of Solidification/Stabilization as a Best Demonstrated Available Technology," *14th Annual Hazardous Waste Engineering Laboratory Conference*, Cincinnati, Ohio.

Wiles, C. C., and E. Barth. 1992. "Solidification/Stabilization: Is It Always Appropriate," in *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*, Vol. 2, ASTM STP 1123, T. M. Gilliam and C. C. Wiles, Eds., American Society for Testing and Materials, Philadelphia, pp. 18-32.

Young, J. F. 1972. "A Review of Mechanisms of Set-Retardation in Portland Cement Pastes Containing Organic Admixtures," *Cement Concrete Res.* 2, 415-433.

Zhou, H., and P. Colombo. 1984. "Solidification of Radioactive Waste in a Cement/Lime Mixture," *Waste Management '84*, pp. 163-168.

DISTRIBUTION

1. L. D. Bates
2. D. T. Bell
3. W. D. Bostick
4. C. H. Brown, Jr.
5. J. L. Collins
6. D. Crenshaw-Smith
7. G. D. Del Cul
8. M. F. P. DeLozier
9. C. W. Francis
10. S. B. Garland
11. T. M. Gilliam
12. C. D. Goins
13. P. J. Halsey
14. D. P. Hoffman
15. B. L. Kimmel
16. V. Legg
- 17-19. D. M. Matteo
- 20-21. P. T. Owen
22. G. E. Rymer
23. P. A. Schrandt
- 24-28. R. D. Spence
29. D. R. Watkins
30. R. K. White
31. Central Research Library
- 32-36. ER Document Management Center
- 37-38. Laboratory Records Dept.
39. ORNL Patent Section
40. ORNL Y-12 Technical Library
41. Office of Assistant Manager for Energy Research and Development, DOE Oak Ridge Field Office, P.O. Box 2001, Oak Ridge, TN 37831-8600
- 42-43. R. L. Nace, Branch Chief, Nonenrichment Facilities, Oak Ridge Program Division, Office of Eastern Area Programs, Office of Environmental Restoration, EM-423, Trevion 2, U.S. Department of Energy, Washington, DC 20585
- 44-45. R. C. Sleeman, DOE Oak Ridge Field Office, P.O. Box 2001, Oak Ridge, TN 37831-8541
- 46-47. J. T. Sweeney, DOE Oak Ridge Field Office, P.O. Box 2001, Oak Ridge, TN 37831-8541
48. D. W. Swindle, Radian Corporation, 120 S. Jefferson Circle, Oak Ridge, TN 37831
- 49-50. H. M. Thron, Chief, Enrichment Facilities, Oak Ridge Program Division, Office of Eastern Area Programs, Office of Environmental Restoration, EM-422, Trevion 2, U.S. Department of Energy, Washington, DC 20585
- 51-55. Susan Trussell, Department of Civil Engineering, Texas A&M University, College Station, TX 77843-3136
- 56-57. Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831

END

DATE
FILMED

5 / 14 / 93