2
WSRC-RP-92-897, REV 1

DWPF PCCS VERSION 2.0 TEST CASE

Received by OSY

JAN 1993

by K. G. Brown

WSRC-RP--92-897-Rev.1

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

DE93 006324

Other Authors:

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

RECEIVED
JAN 1993

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

Memorandum

Keywords: PCCS Version 2.0, Test Case,
DWPF Process Control

Retention Time: Lifetime

cc: L. M. Papouchado, 773-A
E. W. Holtzscheiter, 773-A
M. J. Plodinec, 773-A
L. F. Landon, 704-T
J. T. Carter, 704-1T
C. P. Reeve, 773-42A
F. G. Smith III, 704-1T
C. M. Jantzen, 773-A

PCCS QA File
PMC File
SRL Records (4)

August 13, 1992

TO: C. T. Randall, 704-T

FROM: K. G. Brown, 704-1T ^{Key}
M. A. Pickett, 704-1T ^{MAS}

DWPF PCCS Version 2.0 Test Case (U)

1.0 Introduction and Summary

To verify the operation of the Product Composition Control System (PCCS), a test case specific to DWPF operation was developed. The values and parameters necessary to demonstrate proper DWPF product composition control have been determined and are presented in this paper. If this control information (i.e., for transfers and analyses) is entered into the PCCS as illustrated in this paper, and the results obtained correspond to the independently-generated results, it can safely be said that the PCCS is operating correctly and can thus be used to control the DWPF. The independent results for this test case will be generated and enumerated in a future report.

This test case was constructed along the lines of the normal DWPF operation. Many essential parameters are internal to the PCCS (e.g., property constraint and variance information) and can only be manipulated by personnel knowledgeable of the Symbolics® hardware and software. The validity of these parameters will rely on induction from observed PCCS results. Key process control values are entered into the PCCS as they would during normal operation. Examples of the screens used to input specific process control information are provided. These inputs should be entered into the PCCS database, and the results generated should be checked against the independent, computed results to confirm the validity of the PCCS.

C. T. Randall
Authorized Derivative Classifier

Table of Contents

	<u>page</u>
1.0 Introduction and Summary	1
2.0 PCCS Internal Information	3
2.1 Constraint Information	3
2.2 Miscellaneous Information	6
2.3 Variance Information	6
3.0 Initial PCCS Composition Information	7
3.1 Initializing the PCCS Database for the Test Case	7
3.2 Composition Information for Verification	8
4.0 Determination of the Optimal SRAT Batch 1 Target Blend	9
4.1 Determination of SRAT Batch 1 Target Blend Using the PCCS	9
4.2 Updating the PCCS Transfer Information for SRAT Batch 1	9
5.0 Determination of the Optimal SME Batch 1 Target Blend	12
5.1 Determination of SME Batch 1 Target Blend Using the PCCS	12
5.2 Updating the PCCS Transfer Information for SME Batch 1	12
6.0 Determination of the Optimal SRAT Batch 2 Target Blend	16
6.1 Determination of SRAT Batch 2 Target Blend Using the PCCS	16
6.2 Updating the PCCS Transfer Information for SRAT Batch 2	16
7.0 Determination of the Optimal SME Batch 2 Target Blend	19
7.1 Determination of SME Batch 2 Target Blend Using the PCCS	19
7.2 Updating the PCCS Transfer Information for SME Batch 2	19
8.0 Conclusions	23
Appendix A Normalized Molar Oxide Covariance Matrices	24
Appendix B Elemental Covariance Matrices	28

2.0 PCCS Internal Information

When starting the test case, a new PCCS database should be initialized.¹ All vessels begin with Batch Number equal to 0. This prevents any problems with database consistency and integrity. Within the new database, the following information is internal to the PCCS and should not be manipulated by the user:

2.1 Constraint Information:

The constraint information relevant to DWPF^{2,3} is contained in the **pccs-constraints** flavor instance variable in the DWPF PCCS program frame and the PCCS database.⁴ There is a **pccs-triangle** flavor instance variable containing acceptability region information which is displayed by the PCCS for user information. The processing and product constraint information maintained in the PCCS database is:⁵

Liquidus Temperature:

$$T_L = 803.8698 + 2276.8724 \xi_L \text{ where } \xi_L = \frac{134.00[\text{Fe}_2\text{O}_3]}{155.60[\text{SiO}_2] - 359.88[\text{Al}_2\text{O}_3]}$$

$$s_r = 37.05410 \text{ and } n = 22$$

$$\mathbf{X}_L' \mathbf{X}_L = \begin{bmatrix} 0.4948147 & -5.0556817 \\ -5.0556817 & 56.859585 \end{bmatrix}$$

Thus for the Errorless Property Acceptability Region (EPAR), $T_L \leq 1050^\circ\text{C}$ translates to $\xi_L \leq 0.1081$ or $\underline{\alpha}_L' \leq 0.0$ where

$$\underline{\alpha}_L = [38.9031, 0, 0, 0, 0, 0, 0, 0, 134.0, 0, 0, 0, 0, 0, 0, 0, -16.8204, 0, 0, 0, 0]$$

Backsolving the property constraint regression equation at the 95% confidence interval provides the following parameters necessary to define the Property Acceptability Region (PAR). For the PAR, $T_L \leq 1050^\circ\text{C}$ becomes $\xi_L \leq 0.0971$ (or $T_L \leq 1025^\circ\text{C}$). In composition space, this becomes $\underline{\alpha}_L' \leq 0.0$ where

$$\underline{\alpha}_L = [34.9433, 0, 0, 0, 0, 0, 0, 0, 134.0, 0, 0, 0, 0, 0, 0, 0, -15.1083, 0, 0, 0, 0]$$

¹The procedure for creating a new database is explained in the Section entitled, "PCCS Version 2.0 User Manual" in "DWPF Product Composition Control System (PCCS): Version 2.0 Documentation," WSRC-TR-92-0333, June 22, 1992.

²R. L. Postles and K. G. Brown, "The DWPF Product Composition Control System at Savannah River: Statistical Process Control Algorithm," *Ceramic Transactions, Nuclear Waste Management IV*, Vol. 23, 1991, 559-68.

³Jantzen, C. M. "First Principles Process-Product Models for Vitrification of Nuclear Waste: Relationship of Glass Composition to Glass Viscosity, Resistivity, Liquidus Temperature, and Durability," *Proceedings of the Fifth International Symposium on Ceramics in Nuclear and Hazardous Waste Management*, 1991, 37-51.

⁴Refer to: "DWPF Product Composition Control System (PCCS): Version 2.0 Source Code," WSRC-TR-92-0333, June 22, 1992, on information pertaining to specific PCCS program features.

⁵The positions in the vectors represent the following elements or their corresponding oxides: Al (Al_2O_3), B (B_2O_3), Ba (BaO), Ca (CaO), Cl (NaCl), Cr (Cr_2O_3), Cs (Cs_2O), Cu (CuO), F (NaF), Fe (Fe_2O_3), K (K_2O), Li (Li_2O), Mg (MgO), Mn (MnO), Na (Na_2O), Ni (NiO), P (P_2O_5), S (Na_2SO_4), Si (SiO_2), Th (ThO_2), Ti (TiO_2), U (UO_2), and Zr (ZrO_2). In this information, [i] represents the normalized molar oxide fraction of the ith element, s_r is the rms error from the regression, $\mathbf{X}'\mathbf{X}$ is the product moment matrix, and $\underline{\mathbf{y}}$ is the normalized molar oxide composition vector.

Durability (MCC-1):

$\log(\text{LR}) = 0.45283743 - 0.1637664 \xi_D$ where $\xi_D = \Delta G = y_{aD}'$ and

$$a_D = [3.04, -9.93, 0, -21.706, 0, 0, 0, 0, 15.5, -52.915, -28.33, -19.478, -20.461, -34.405, -19.937, 0, 0, 5.59, 0, 15.99, 0, 39.51]$$

$s_r = 0.4398606$ and $n = 304$

$$X_D'X_D = \begin{bmatrix} 0.010069735 & 0.0014917752 \\ 0.0014917752 & 0.0003282164 \end{bmatrix}$$

Thus for the Durability EPAR,⁶ $\log(\text{LR}) \leq 1.4472$ translates to $\xi_D \leq -6.0716$ or $y_{aD}' \leq -6.0716$. Backsolving the property constraint regression equation at the 95% confidence interval provides the following parameters necessary to define the PAR. For the PAR, $\log(\text{LR}) \leq 1.4472$ becomes $\xi_D \leq -5.6077$ (or $\log(\text{LR}) \leq 1.3712$). In composition space, this becomes $y_{aD}' \leq -5.6077$.⁷

Viscosity (at 1150°C):

$\log(\eta) = 3.28650094 - 1.53421247 \xi_V$

$$\text{where } \xi_V = \frac{2([\text{Fe}_2\text{O}_3] - [\text{Al}_2\text{O}_3] + [\text{K}_2\text{O}] + [\text{Li}_2\text{O}] + [\text{Na}_2\text{O}]) + [\text{B}_2\text{O}_3]}{[\text{SiO}_2]}$$

$s_r = 0.0736389$ and $n = 213$

$$X_V'X_V = \begin{bmatrix} 0.3876 & -380.173 & -0.049 \\ -380.173 & 512631.3 & -73.7299 \\ -0.049 & -73.7299 & 0.1171 \end{bmatrix}$$

For the High Viscosity EPAR, $\eta \leq 100$ poise (or $\log(\eta) \leq 2.0$) translates to $\xi_{HV} \geq 0.8334$ or $y_{aHV}' \geq 0.0$ where

$$a_{HV} = [-2, 1, 0, 0, 0, 0, 0, 0, 2, 2, 2, 0, 0, 2, 0, 0, 0, -0.8334, 0, 0, 0, 0]$$

Backsolving the property constraint regression equation at the 95% confidence interval provides the following parameters necessary to define the High Viscosity PAR. For the PAR, $\log(\eta) \leq 2.0$ becomes $\xi_{HV} \geq 0.8447$ (or $\eta \leq 97.9$ poise). In composition space, this becomes $y_{aHV}' \leq 0.0$ where

$$a_{HV} = [-2, 1, 0, 0, 0, 0, 0, 0, 2, 2, 2, 0, 0, 2, 0, 0, 0, -0.8447, 0, 0, 0, 0]$$

For the Low Viscosity EPAR, $\eta \geq 20$ poise (or $\log(\eta) \geq 1.301$) translates to $\xi_{LV} \leq 1.2890$ or $y_{aLV}' \leq 0.0$ where

$$a_{LV} = [-2, 1, 0, 0, 0, 0, 0, 0, 2, 2, 2, 0, 0, 2, 0, 0, 0, -1.2890, 0, 0, 0, 0]$$

Backsolving the property constraint regression equation at the 95% confidence interval provides the parameters necessary to define the Low Viscosity PAR. For the PAR, $\log(\eta) \geq 1.301$ becomes $\xi_{LV} \leq 1.2715$ (or $\eta \geq 21.7$ poise). In composition space, this becomes $y_{aLV}' \leq 0.0$ where

$$a_{LV} = [-2, 1, 0, 0, 0, 0, 0, 0, 2, 2, 2, 0, 0, 2, 0, 0, 0, -1.2715, 0, 0, 0, 0]$$

⁶The units of the leach rate (LR) are $\text{g/m}^2\text{-28days}$.

⁷For durability, $\alpha_D = a_D$.

Waste Solubility Criteria:

There is no modeling error in the waste solubility criteria; therefore, all that is necessary is to convert the solubility constraint on glass composition from a mass to a molar basis.⁸ The new constraints are as follows:

$\text{TiO}_2 \leq 1.0 \text{ wt\%}$ in the glass becomes $y_{\text{aTi}}' \leq 0.0$ where

$$\underline{a}_{\text{Ti}} = [-1.0196, -0.6962, -1.5334, -0.5608, -0.5844, -1.5199, -2.8181, -0.7954, -0.4199, -1.5969, \\ -0.9420, -0.2988, -0.4031, -0.7094, -0.6198, -0.7471, -1.4194, -1.4204, -0.6008, -2.6404, \\ 79.0998, -2.7004, -1.2322]$$

$\text{Na}_2\text{SO}_4 < 0.59 \text{ wt\%}$ in the glass⁹ becomes $y_{\text{aS}}' \leq 0.0$ where

$$\underline{a}_{\text{S}} = [-0.6016, -0.4108, -0.9047, -0.3309, -0.3448, -0.8967, -1.6627, -0.4693, -0.2477, -0.9422, \\ -0.5558, -0.1763, -0.2378, -0.4185, -0.3657, -0.4408, -0.8375, 141.2032, -0.3545, -1.5578, \\ -0.4714, -1.5932, -0.7270]$$

$\text{Cr}_2\text{O}_3 < 0.30 \text{ wt\%}$ in the glass becomes $y_{\text{aCr}}' \leq 0.0$ where

$$\underline{a}_{\text{Cr}} = [-0.3059, -0.2089, -0.4600, -0.1682, -0.1753, 151.5342, -0.8454, -0.2386, -0.1260, -0.4791, \\ -0.2826, -0.0896, -0.1209, -0.2128, -0.1859, -0.2241, -0.4258, -0.4261, -0.1803, -0.7921, \\ -0.2397, -0.8101, -0.3697]$$

$\text{P}_2\text{O}_5 < 3.0 \text{ wt\%}$ in the glass becomes $y_{\text{aP}}' \leq 0.0$ where

$$\underline{a}_{\text{P}} = [-3.0588, -2.0886, -4.6002, -1.6824, -1.7533, -4.5597, -8.4543, -2.3862, -1.2596, -4.7908, \\ -2.8261, -0.8963, -1.2093, -2.1281, -1.8594, -2.2413, -137.686, -4.2612, -1.8025, -7.9211, \\ -2.3970, -8.1012, -3.6966]$$

$\text{NaCl} < 1.0 \text{ wt\%}$ in the glass becomes $y_{\text{aCl}}' \leq 0.0$ where

$$\underline{a}_{\text{Cl}} = [-1.0196, -0.6962, -1.5334, -0.5608, 57.8584, -1.5199, -2.8181, -0.7954, -0.4199, -1.5969, \\ -0.9420, -0.2988, -0.4031, -0.7094, -0.6198, -0.7471, -1.4194, -1.4204, -0.6008, -2.6404, \\ -0.7990, -2.7004, -1.2322]$$

$\text{NaF} < 1.0 \text{ wt\%}$ in the glass becomes $y_{\text{aF}}' \leq 0.0$ where

$$\underline{a}_{\text{F}} = [-1.0196, -0.6962, -1.5334, -0.5608, -0.5844, -1.5199, -2.8181, -0.7954, -41.5683, -1.5969, \\ -0.9420, -0.2988, -0.4031, -0.7094, -0.6198, -0.7471, -1.4194, -1.4204, -0.6008, -2.6404, \\ -0.7990, -2.7004, -1.2322]$$

$\text{Cu} < 0.5$ (or $\text{CuO} \leq 0.6259$) $\text{wt\%}$ in the glass becomes $y_{\text{aCu}}' \leq 0.0$ where

$$\underline{a}_{\text{Cu}} = [-0.6382, -0.4358, -0.9598, -0.3510, -0.3658, -0.9513, -1.7638, 79.0416, -0.2628, -0.9995, \\ -0.5896, -0.1870, -0.2523, -0.4440, -0.3879, -0.4676, -0.8884, -0.8890, -0.3761, -1.6526, \\ -0.5001, -1.6902, -0.7712]$$

⁸Brown, K. G. "Converting the Waste Solubility Constraints to a Form Useful for the PCCS," SRTC-PMC-92-0007, May 15, 1992.

⁹This is actually the SO_4 constraint converted to a constraint on Na_2SO_4 since this is what we maintain in PCCS.

2.2 Miscellaneous Information

The following miscellaneous information is necessary to determine the PCCS blending strategy:

$\underline{M}$ = [101.9612, 69.6202, 153.3394, 56.0794, 58.4428, 151.9902, 281.8094, 79.5394, 41.9882, 159.6922, 94.2034, 29.8774, 40.3114, 70.9374, 61.979, 74.7094, 141.9446, 142.0412, 60.0848, 264.0368, 79.8988, 270.0388, 123.2188]

$\underline{\gamma}$ = [1.8895, 3.2199, 1.1165, 1.3992, 1.6485, 1.4612, 1.0602, 1.2518, 2.2101, 1.4297, 1.2046, 2.1529, 1.6581, 1.2912, 1.3480, 1.2725, 2.2914, 4.4230, 2.1393, 1.1379, 1.6680, 1.1344, 1.3508]

where $\underline{M}$ is the array of molecular weights of oxide species, and $\underline{\gamma}$ contains the gravimetric factors converting the species from elements to oxides on a weight basis.

2.3 Variance Information:

The initial variance information necessary to define the optimal blending target, remediate SME batches, and monitor SME product is internal to the PCCS. Applicable variance information is updated during PCCS operation to represent the current DWPF state. To determine the optimal SRAT target blend, the Tank 51 or sludge covariance matrix, Precipitate Reactor Bottoms Tank (PRBT) or PHA covariance matrix, Process Frit Slurry Feed Tank (PFSFT) or frit covariance matrix, and the SRAT Heel covariance matrix are needed.¹⁰ This covariance information in terms of normalized molar oxides is supplied in Appendix A.

Upon determining the optimal SRAT target blend, the prescribed amounts of sludge and PHA will be added to the SRAT Heel. The SRAT product composition can be estimated from the transfer information, and a measurement of the composition will also be collected and analyzed. These composition estimates can be combined using a Maximum A Posteriori (MAP) estimator to provide the best possible estimate of the SRAT product composition.¹¹ For computational purposes, the elemental covariance matrices are used to determine the MAP composition estimate from which the equivalent normalized molar oxide composition can be computed.¹² These elemental covariances are provided in Appendix B.

¹⁰The SRAT Heel covariance information is the same as that for the SRAT product covariance matrix since a heel analysis is not taken for the SRAT for blending purposes.

¹¹R. L. Postles and K. G. Brown, "PCCS SPC Algorithms for Waste Compliance," SCS-PMG-91097, December 4, 1991.

¹²Normalized molar oxide compositions are used in the property correlations. When the covariance matrix for such data is computed, the additional normalization constraint causes the covariance matrix to be uniquely singular and cannot thus be inverted. One way around this is to normalize over more elements than would be inverted; however, depending on the elements remaining, the resulting matrix may be highly ill-conditioned. In other words, the result of inverting the covariance matrix will be very sensitive to small changes in input values and thus is not useful for process control.

3.0 Initial PCCS Composition Information

The PCCS will be validated based on typical SRAT and SME blends; the operations necessary to complete an acceptable SME batch encompass those steps necessary to assure that the PCCS is operating properly. Since the SRAT and SME blending steps are of primary concern, it will be satisfactory to assume that PRBT and PFSFT products are present at the beginning of the test case.

3.1 Initializing the PCCS Database for the Test Case

In DWPF operation, many steps are necessary to derive PRBT and PFSFT product compositions - steps that are not necessary for the current test case as it is posed. To facilitate the generation of these compositions, the following command must be entered in the PCCS Command Line:

PCCS Command: (initialize-for-testing dw:*program*) <Enter>

This command is defined in the PCCS test program additions file as follows:¹³

```
(defmethod (initialize-for-testing pccs) ()
  (record-new-vessel-batch self 'baft)
  (record-new-slurry-analysis self 'baft baft ; 5% Boric Acid FT analysis
    '(B 8742.1))
    5.0 2.73 1.05 "5% Boric Acid" 'product 'ppm)
  (record-new-vessel-batch self 'kft)
  (record-new-slurry-analysis self 'kft kft ; 45% KOH FT analysis
    '(K 313600.0))
    45.0 37.76 1.46 "45% KOH Solution" 'product 'ppm)
  (record-new-vessel-batch self 'naft)
  (record-new-slurry-analysis self 'naft naft ; 50% Caustic FT analysis
    '(NA 287394.0))
    50.0 38.74 1.52 "50% NaOH Solution" 'product 'ppm)
  (record-new-vessel-batch self 'tank-51)
  (record-new-slurry-analysis self 'tank-51 tank-51 ; sludge analysis
    '(AL 7.49) (B 0.0) (BA 0.184) (CA 2.575) (CL 0.729) (CR 0.205)
    (CS 0.0) (CU 0.125) (F 0.15) (FE 26.204) (K 0.311) (LI 0.0) (MG 0.195)
    (MN 4.774) (NA 8.049) (NI 1.764) (P 0.035) (S 0.25) (SI 1.77)
    (TH 0.952) (TI 0.0) (U 1.328) (ZR 0.0)
    15.4 13.08 1.10 "Tank-51-P-1" 'product)
  (record-new-vessel-batch self 'prbt)
  (record-new-slurry-analysis self 'prbt prbt ; PHA analysis in ppm
    '(AL 7.35) (B 1820.0) (BA 0.0) (CA 0.0) (CL 0.93) (CR 0.15) (CS 201.3)
    (CU 802.0) (F 0.35) (FE 0.0) (K 5999.3) (LI 0.0) (MG 0.0) (MN 0.0)
    (NA 436.1) (NI 0.0) (P 0.23) (S 4.02) (SI 0.08) (TH 0.0) (TI 674.4)
    (U 0.0) (ZR 0.0))
    3.87 1.61 1.02 "PRBT-P-1" 'product 'ppm)
  (record-new-vessel-batch self 'pfsft) ; new PFSFT batch
  (record-new-slurry-analysis self 'pfsft pfsft ; PFSFT analysis, calcined%
    '(AL 0.0) (B 2.48) (BA 0.0) (CA 0.0) (CL 0.0) (CR 0.0) (CS 0.0)
    (CU 0.0) (F 0.0) (FE 0.0) (K 0.0) (LI 3.25) (MG 1.21) (MN 0.0)
    (NA 4.45) (NI 0.0) (P 0.0) (S 0.0) (SI 35.99) (TH 0.0) (TI 0.0)
    (U 0.0) (ZR 0.0))
    60.0 60.0 1.50 "PFSFT-P-1" 'product 'wt%-oxides)
  (record-new-vessel-batch self 'srat) ; new SRAT batch
  (record-new-vessel-batch self 'sme) ; new SME batch
  (record-new-vessel-batch self 'smect) ; new SPECT batch
  (record-new-vessel-batch self 'mft)) ; new MFT batch
```

¹³I refer to this specific function since it is non-standard PCCS code needed only for this test case.

This command places the Tank-51, PRBT, and PFSFT compositions in the database and creates new batches for the vessels used in the test case. The trim chemicals are also entered into the PCCS database (i.e., BAFT, KFT, and NAFT) for any remediation purposes. The PCCS Detailed Display or Data Entry Display can be utilized to assure that the information has been entered correctly.

3.2 Composition Information for Verification

Since the Tank-51, PRBT, and PFSFT products exist, the correct quantities of PRBT (p), Tank-51 (s), and PFSFT (f) material to add to the SRAT Heel (h) must be determined using the PCCS. This is referred to as the optimal (h,p,s,f) blend. However on the initial run, there is no SRAT Heel present. Therefore, the optimal (p,s,f) blend must be determined. The composition information for these feed streams is:¹⁴

PRBT Batch 1 Product

$\underline{x}^p = [7.35 \ 1820.0 \ 0.0 \ 0.0 \ 0.93 \ 0.15 \ 201.3 \ 802.0 \ 0.35 \ 0.0 \ 5999.3 \ 0.0 \ 0.0 \ 0.0 \ 436.1 \ 0.0 \ 0.23 \ 4.02 \ 0.08 \ 0.0 \ 674.4 \ 0.0 \ 0.0]$
 $\rho_p = 1.02$, $\omega_p = 3.87$, and $c_p = 1.61$

Tank-51 Batch 1 Product:

$\underline{x}^s = [7.49 \ 0.0 \ 0.184 \ 2.575 \ 0.729 \ 0.205 \ 0.0 \ 0.125 \ 0.15 \ 26.204 \ 0.311 \ 0.0 \ 0.195 \ 4.774 \ 8.049 \ 1.764 \ 0.035 \ 0.25 \ 1.77 \ 0.952 \ 0.0 \ 1.328 \ 0.0]$
 $\rho_s = 1.10$, $\omega_s = 15.4$, and $c_s = 13.08$

PFSFT Batch 1 Product:

$\underline{x}^f = [0, 2.48, 0, 0, 0, 0, 0, 0, 0, 0, 3.25, 1.21, 0, 4.45, 0, 0, 0, 35.99, 0, 0, 0]$
 $\rho_f = 1.50$, $\omega_f = 60.0$, and $c_f = 60.0$

In this composition information, $\underline{x}^i$ represents the elemental composition, ρ_i the specific gravity, ω_i the weight percent solids, and c_i the calcined weight percent solids for the i^{th} stream (e.g., SRAT Heel or r, Tank-51 Sludge or s, etc.).

¹⁴This is the same information entered into the PCCS Database by `initialize-for-testing` function as discussed in Section 3.1

4.0 Determination of the Optimal SRAT Batch 1 Target Blend

The optimal fractions of PRBT and Tank 51 material to blend in the SRAT (as well as the correct amount of PFSFT material that would be blended in the SME), i.e., the optimal ($\tau_h, \tau_p, \tau_s, f$) blend, will be determined using the PCCS. Here τ is the fraction of the SRAT material transferred to the SME.

4.1 Determination of SRAT Batch 1 Target Blend Using the PCCS

To determine the optimal blend of PRBT, Tank 51, and PFSFT material, the PCCS Batching Display is used. Once in the Batching Display, the "Compute SRAT Batching Quantities" command is either selected using the mouse or typed into the command line. "PRECIPITATE" should be chosen as the material to be optimized, the Target Sludge volume should be 6500.0 gallons, and the maximum PRBT volume should be set to 10530.0 gallons.¹⁵ The optimal blend and related information is then computed using this information¹⁶ and displayed in the right-hand window under the heading: **Batching Information for SRAT Batch 1**. This includes the following blend information:

SRAT Target Information

Wgt Frac	Wgt Frac	Wgt Frac	Comment
PHA	Sludge	Frit	
.049	.293	.658	Liquidus Temperature

SRAT Volumetric Target Information

Gallons	Gallons	Gallons	Comment
PHA	Sludge	Frit	
12960.0	8831.2	2571.0	Liquidus Temperature

and the relevant compositions and SRAT target properties.

4.2 Updating the PCCS Transfer Information for SRAT Batch 1

The information in the PCCS database must be updated to account for the transfers described in the SRAT volumetric target from Section 4.1. For a 6500.0 gallon SRAT to SME transfer, 8831.2 gallons of Sludge from Tank-51 and 12960.0 gallons of PRBT material are necessary to produce acceptable melter feed in the SME with 2571.0 gallons of PFSFT material. These transfers are recorded using the PCCS Data Entry Display.

To enter the sludge transfer information, the "Enter New Transfer" command is selected, Tank-51 is selected as the source vessel, and the SRAT is selected as the target vessel. The relevant transfer information is then entered:¹⁷

¹⁵The defaults for the sludge and PRBT volumes are 5000.0 and 8100.0 gallons, respectively. Since there is no SRAT heel, it is necessary to add more sludge and PHA to the initial SRAT batch to compensate. This will produce SRAT and SME batches close to the steady-state batch for this sludge and PHA combination.

¹⁶That is, if the composition information has been initialized; otherwise, a warning to this effect will be made, and no SRAT target will be found.

¹⁷Since 8831.2 gallons of sludge from Tank-51 is outside the range of 5000-8000 gallons, the Supervisory Permissive will have to be utilized for the Tank-51 to SRAT transfer.

New Transfer Data for TANK-51 to SRAT Transfer			
Information for Source Vessel TANK-51 Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.05-1.22		: 1.1
Volume Transferred from Source Tank	5000-8000	Gal	: 8831.2
Information for Target Vessel SRAT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.1-1.25		: 1.0
Target Tank Initial Volume	1300-1800	Gal	: 0.
Target Tank Material Final Specific Gravity	1.05-1.2		: 1.1
Target Tank Final Volume	6000-9000	Gal	: 8831.2
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The information in the PCCS database is updated and can be verified using the Data Entry Display or the Detailed Data Display. The PHA transfer from the PRBT to the SRAT is recorded similarly:¹⁸

New Transfer Data for PRBT to SRAT Transfer			
Information for Source Vessel PRBT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.9-1.1		: 1.02
Volume Transferred from Source Tank	7000-10000	Gal	: 12960.0
Information for Target Vessel SRAT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.05-1.2		: 1.1
Target Tank Initial Volume	6000-9000	Gal	: 8831.2
Target Tank Material Final Specific Gravity	1.1-1.25		: 1.0524
Target Tank Final Volume	5000-8000	Gal	: 21791.2
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The Detailed Display can again be used to verify the information for SRAT Batch 1. No measured SRAT composition has been recorded; however, the PCCS automatically updates the composition prediction for the vessel whenever a transfer is recorded. With no measurement, the best (or MAP) estimate of the SRAT composition is the same as the predicted measurement. Finally, to assure that the vessel is ready for product transfer and sampling, the contents are concentrated (i.e., water is transferred from the SRAT to the SMECT) until the SRAT volume is 8000.0 gallons:¹⁹

¹⁸To simplify matters somewhat, all additions will be made to the vessel in question and then a single final concentration step will be employed. Again the Supervisory Permissive is necessary.

¹⁹This allows 6500 gallons of SRAT material to be transferred to the SME which currently has no heel.

New Transfer Data for SRAT to SMECT Transfer				
Information for Source Vessel SRAT Batch 1				
Item	Range	Units	Value	
Transfer-ID			: TRNSFR2168	
Source Material Specific Gravity	0.9-1.5		: 1.0524	
Volume Transferred from Source Tank	0-10000	Gal	: 13791.2	
Information for Target Vessel SMECT Batch 1				
Item	Range	Units	Value	
Target Tank Material Initial Specific Gravity	0.9-1.1		: 1.0	
Target Tank Initial Volume	0-10000	Gal	: 0.	
Target Tank Material Final Specific Gravity	0.9-1.1		: 1.0	
Target Tank Final Volume	0-10000	Gal	: 13791.2	
<i>Operations</i>				
Select for Supervisor Permissive to Override Data Ranges				
Done		Abort		

Processing for SRAT Batch 1 is now complete. The final step in the SRAT cycle is to sample the SRAT material and record the results in the PCCS database. The SRAT Product analysis is entered into the PCCS using the Data Entry Display. The "Enter New Analysis" command is selected, and the SRAT is chosen as the vessel. This is the SRAT "Product" sample. The following information is entered:

New Sample Analysis for SRAT				
Sample Analysis for SRAT in WT%-SOLIDS				
Item	Range	Units	Value	
Sample-ID			: Sample4705	
Sample Type			: Receipt Product	
Wgt% Solids	15.0-25.0		: 22.0	
Calcined Wgt% Solids	0.0-25.0		: 16.25	
Specific Gravity	1.05-1.25		: 1.14	
AL	0.0-10.0	Wt%	: 5.6	
B	0.0-5.0	Wt%	: 1.25	
FE	15.0-25.0	Wt%	: 19.5	
K	0.0-5.0	Wt%	: 4.2	
<i>Operations</i>				
Select for Supervisor Permissive to Override Data Ranges				
Done		Abort		

After the sample measurement is entered, the SRAT contains 8000.0 gallons of material with the measured, predicted and best compositions as shown in the PCCS Detailed Display for SRAT Batch 1. The covariance matrices associated with the projected and best SRAT compositions have been computed and stored in the PCCS database. Now the first SME batch can be prepared.

5.0 Determination of the Optimal SME Batch 1 Target Blend

For SRAT Batch 1, the optimal (p,s,f) blend was determined since no SME Heel was present. For SME Batch 1, the optimal combination of SRAT and PFSFT material must be determined since there is also no heel in the SME to begin. The SRAT and PFSFT composition information has not changed from SRAT Batch 1. The information necessary to compute the optimal (r,f) target for SME Batch 1 is available.

5.1 Determination of SME Batch 1 Target Blend Using the PCCS

The optimal blend of SRAT and PFSFT material that produces acceptable melter feed material for SME Batch 1 must be determined. However, these quantities were already defined in the previous SRAT Batch 1 target determination. For this target blend, it was specified that 6500.0 gallons of SRAT material would be transferred from the SRAT to the SME and the correct amount of PFSFT material was determined.

5.2 Updating the PCCS Transfer Information for SME Batch 1

The transfer information for SME Batch 1 must be stored in the PCCS database. For a 6500.0 gallon SRAT transfer, 2571.0 gallons of PFSFT material are needed to produce acceptable melter feed material. The PCCS Data Entry Display is used to record this information. For the SRAT to SME transfer, the "Enter New Transfer" command is selected, the "SRAT" is selected as source vessel and the "SME" as the target vessel. Then the relevant transfer information is entered:

New Transfer Data for SRAT to SME Transfer			
Information for Source Vessel SRAT Batch 1			
Item	Range	Units	Value
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.1-1.25		: 1.142
Volume Transferred from Source Tank	5000-7000	Gal	: 6500.0
Information for Target Vessel SME Batch 1			
Item	Range	Units	Value
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.0
Target Tank Initial Volume	0-1800	Gal	: 0.
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.142
Target Tank Final Volume	5500-7000	Gal	: 6500.0
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

This concludes the SRAT Batch 1 cycle. To create a new SRAT batch for subsequent processing, "Start New Batch" for the SRAT are chosen from the Data Entry Display. Finally the new SRAT batch is confirmed using the mouse.

For the PFSFT transfer, the following information is recorded:

New Transfer Data for PFSFT to SME Transfer			
Information for Source Vessel PFSFT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.92-1.13		: 1.5
Volume Transferred from Source Tank	1400-2000	Gal	: 2571.0
Information for Target Vessel SME Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.142
Target Tank Initial Volume	1300-1800	Gal	: 6500.0
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.2435
Target Tank Final Volume	5500-7000	Gal	: 9071.0
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The Detailed Display can be used to verify that the information for SME Batch 1 has been entered correctly. Thus far there is no measured SME composition; however, the PCCS automatically updates the composition prediction for the SME. With no measurement, the best estimate of the SME composition is the same as the predicted measurement. The contents are concentrated (i.e., water transferred to the SMECT) until the SME volume equals 6500.0 gallons:

New Transfer Data for SME to SMECT Transfer			
Information for Source Vessel SME Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.9-1.5		: 1.2435
Volume Transferred from Source Tank	0-10000	Gal	: 2571.0
Information for Target Vessel SMECT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	0.9-1.1		: 1.0
Target Tank Initial Volume	0-10000	Gal	: 0.
Target Tank Material Final Specific Gravity	0.9-1.1		: 1.0
Target Tank Final Volume	0-10000	Gal	: 2571.0
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

Processing for SME Batch 1 is now complete. The final step is to sample the SME material and test the composition for acceptability. The SME analysis is entered into the PCCS using the Data Entry Display. The "Enter New Analysis" command is selected and the SME is chosen as the vessel. The following data are entered:

New Sample Analysis for SME			
Sample Analysis for SME in WT%-OXIDES			
Item	Range	Units	Value
Sample-ID			: Sample-705
Wgt% Solids	38.0-47.0		: 45.4
Calcined Wgt% Solids	0.0-47.0		: 40.52
Specific Gravity	1.2-1.5		: 1.35
AL	0.0-50.0	Wt%	: 2.59
B	0.0-50.0	Wt%	: 2.19
CA	0.0-50.0	Wt%	: 0.89
FE	0.0-50.0	Wt%	: 8.90
K	0.0-50.0	Wt%	: 1.94
LI	0.0-50.0	Wt%	: 2.14
MG	0.0-50.0	Wt%	: 0.86
MN	0.0-50.0	Wt%	: 1.65
NA	0.0-50.0	Wt%	: 5.84
NI	0.0-50.0	Wt%	: 0.61
SI	0.0-50.0	Wt%	: 24.50
TI	0.0-50.0	Wt%	: 0.21
U	0.0-50.0	Wt%	: 0.46
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

After the sample measurement is entered, the SME contains 6500.0 gallons of material with the measured, predicted and best compositions as shown in the Detailed Display for SME Batch 1.

From the Batching Display, the "Determine SME Acceptability" command is selected, and the right-hand window summarizes the relevant acceptability information for the target composition. The information computed for the Property and Measurement Acceptability tests can be presented by clicking the middle mouse button on the Acceptability titles to display all output fields. Since the PCCS indicates that this material possesses acceptable predicted properties, 5000.0 gallons of acceptable melter feed material can be transferred to the MFT. From the Data Entry Display, the "Enter New Transfer" command is selected for the SME. The following information is entered:

New Transfer Data for SME to MFT Transfer			
Information for Source Vessel SME Batch 1			
Item	Range	Units	Value
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.2-1.5		: 1.35
Volume Transferred from Source Tank	4500-7000	Gal	: 5000.0
Information for Target Vessel MFT Batch 1			
Item	Range	Units	Value
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.0
Target Tank Initial Volume	0-1800	Gal	: 0.
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.35
Target Tank Final Volume	4500-7000	Gal	: 5000.0
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

This concludes the SME Batch 1 cycle. A new SME Batch is now commenced by choosing the "Start New Batch" command from the Data Entry Display and confirming. Now the second SRAT and SME batches can be processed using the PCCS.

6.0 Determination of the Optimal SRAT Batch 2 Target Blend

The optimal amounts of PRBT and Tank 51 material to blend with the SRAT Heel (as well as the correct amount of PFSFT material that should be added to the SME), i.e., the optimal (h,p,s,f) blend, will be determined using the PCCS.

6.1 Determination of SRAT Batch 2 Target Blend Using the PCCS

To determine the optimal blend of SRAT Heel, PRBT, Tank 51, and PFSFT material, the PCCS Batching Display is again used. Once in the Batching Display, the "Compute SRAT Batching Quantities" command is selected using the mouse. "PRECIPITATE" should be chosen as the material to be optimized, the Target Sludge volume should be the default 5000.0 gallons, and the maximum PRBT volume should be set to the default 8100.0 gallons. The optimal SRAT target blend and related information is then computed using this information and displayed in the right-hand window under the heading: **Batching Information for SRAT Batch 2**. This includes the following blend information:

SRAT Target Information

Wgt Frac	Wgt Frac	Wgt Frac	Wgt Frac	Comment
Heel	PHA	Sludge	Frit	
.079	.038	.227	.655	Liquidus Temperature

SRAT Volumetric Target Information

Gallons	Gallons	Gallons	Gallons	Comment
Heel	PHA	Sludge	Frit	
1500.0	8100.0	5519.2	1959.3	Liquidus Temperature

and the relevant compositions and SRAT target properties.

6.2 Updating the PCCS Transfer Information for SRAT Batch 2

The information in the PCCS database must be updated to account for the transfers described in the SRAT volumetric target. For a 5000.0 gallon SRAT to SME transfer, 5519.2 gallons of Sludge from Tank-51 and 8100.0 gallons of PRBT material are necessary to produce acceptable melter feed in the SME with 1959.3 gallons of PFSFT material. These transfers associated with the SRAT are recorded using the PCCS Data Entry Display.

To enter the sludge transfer information, the "Enter New Transfer" command is selected, Tank-51 is selected as the source vessel, and the SRAT is selected as the target vessel. The relevant transfer information is then entered:

New Transfer Data for TANK-51 to SRAT Transfer			
Information for Source Vessel TANK-51 Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.05-1.22		: 1.1
Volume Transferred from Source Tank	5000-8000	Gal	: 5519.5
Information for Target Vessel SRAT Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.1-1.25		: 1.142
Target Tank Initial Volume	1300-1800	Gal	: 1500.0
Target Tank Material Final Specific Gravity	1.05-1.2		: 1.109
Target Tank Final Volume	6000-9000	Gal	: 7019.5
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The information in the PCCS database is updated and can be verified using the Data Entry Display or the Detailed Data Display. The PHA transfer from the PRBT to the SRAT is recorded similarly:²⁰

New Transfer Data for PRBT to SRAT Transfer			
Information for Source Vessel PRBT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.9-1.1		: 1.02
Volume Transferred from Source Tank	7000-10000	Gal	: 8100.0
Information for Target Vessel SRAT Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.05-1.2		: 1.109
Target Tank Initial Volume	6000-9000	Gal	: 7019.5
Target Tank Material Final Specific Gravity	1.1-1.25		: 1.0613
Target Tank Final Volume	5000-8000	Gal	: 15119.5
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The Detailed Display can again be used to verify the information for SRAT Batch 2. No measured SRAT composition has been recorded; however, the PCCS automatically updates the composition prediction for the vessel whenever a transfer is recorded. With no measurement, the best (or MAP) estimate of the SRAT composition is the same as the predicted measurement. Finally, to assure that the vessel is ready for product transfer and sampling, the contents are concentrated (i.e., water is transferred from the SRAT to the SMECT) until the SRAT volume is 6500.0 gallons:

²⁰To simplify matters somewhat, all additions will be made to the vessel in question and then a single final concentration step will be employed. The Supervisory Permissive is necessary to effect this transfer.

New Transfer Data for SRAT to SMECT Transfer			
Information for Source Vessel SRAT Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.9-1.5		: 1.0613
Volume Transferred from Source Tank	0-10000	Gal	: 8619.5
Information for Target Vessel SMECT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	0.9-1.1		: 1.0
Target Tank Initial Volume	0-10000	Gal	: 0.
Target Tank Material Final Specific Gravity	0.9-1.1		: 1.0
Target Tank Final Volume	0-10000	Gal	: 8619.5
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

Processing for SRAT Batch 2 is now complete. The final step in the SRAT cycle is to sample the SRAT material and record the results in the PCCS database. The SRAT Product analysis is entered into the PCCS using the Data Entry Display. The "Enter New Analysis" command is selected, and the SRAT is chosen as the vessel. This is the SRAT "Product" sample. The following information is entered:

New Sample Analysis for SRAT			
Sample Analysis for SRAT in WT%-SOLIDS			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Sample-ID			: Sample4705
Sample Type			: Receipt Product
Wgt% Solids	15.0-25.0		: 22.0
Calcined Wgt% Solids	0.0-25.0		: 16.25
Specific Gravity	1.05-1.25		: 1.14
AL	0.0-10.0	Wt%	: 5.65
B	0.0-5.0	Wt%	: 1.2
FE	15.0-25.0	Wt%	: 19.51
K	0.0-5.0	Wt%	: 4.21
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

After the sample measurement is entered, the SRAT contains 6500.0 gallons of material with the measured, predicted and best compositions as shown in the PCCS Detailed Display for SRAT Batch 2. The covariance matrices associated with the projected and best SRAT compositions have been computed and stored in the PCCS database. Now the second SME batch can be prepared.

7.0 Determination of the Optimal SME Batch 2 Target Blend

For SRAT Batch 2, the optimal (h,p,s,f) blend was determined. For SME Batch 2, the optimal combination of SME Heel, SRAT and PFSFT material must be determined. The PFSFT composition information has not changed from SRAT Batch 1. The information necessary to compute the optimal (m,r,f) target for SME Batch 2 is available.

7.1 Determination of SME Batch 2 Target Blend Using the PCCS

To determine the optimal blend of SME Heel, SRAT, and PFSFT material, the PCCS Batching Display is again used. Once in the Batching Display, the "Compute SME Batching Quantities" command is selected using the mouse. The defaults should be used for this particular blend. The optimal SME target blend and related information is then computed using this information and displayed in the right-hand window under the heading: **Batching Information for SME Batch 2**. This includes the following blend information:

SME Target Information

Wgt Frac	Wgt Frac	Wgt Frac	Comment
SME Heel	SRAT	Frit	
.230	.261	.509	Liquidus Temperature

SME Volumetric Target Information

Gallons	Gallons	Gallons	Gallons	Comment
SME Heel	SRAT	Frit	Decon	
1500.0	5000.0	2006.7	.0	Liquidus Temperature

7.2 Updating the PCCS Transfer Information for SME Batch 2

The transfer information for SME Batch 2 must be stored in the PCCS database. For a 5000.0 gallon SRAT transfer, 2006.7 gallons of PFSFT material are needed to produce acceptable melter feed material. The PCCS Data Entry Display is used to record this information. For the SRAT to SME transfer, the "Enter New Transfer" command is selected, the "SRAT" is selected as source vessel and the "SME" as the target vessel. Then the relevant transfer information is entered:

New Transfer Data for SRAT to SME Transfer			
Information for Source Vessel SRAT Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.1-1.25		: 1.142
Volume Transferred from Source Tank	5000-7000	Gal	: 5000.0
Information for Target Vessel SME Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.341
Target Tank Initial Volume	0-1800	Gal	: 1500.0
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.1879
Target Tank Final Volume	5500-7000	Gal	: 6500.0
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

This concludes the SRAT Batch 2 cycle. To create a new SRAT batch for subsequent processing, "Start New Batch" for the SRAT are chosen from the Data Entry Display. Finally the new SRAT batch is confirmed using the mouse.

For the PFSFT transfer, the following information is recorded:

New Transfer Data for PFSFT to SME Transfer			
Information for Source Vessel PFSFT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.92-1.13		: 1.5
Volume Transferred from Source Tank	1400-2000	Gal	: 2006.7
Information for Target Vessel SME Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.1879
Target Tank Initial Volume	1300-1800	Gal	: 6500.0
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.2615
Target Tank Final Volume	5500-7000	Gal	: 8506.7
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

The Detailed Display can be used to verify that the information for SME Batch 2 has been entered correctly. Thus far there is no measured SME composition; however, the PCCS automatically updates the composition prediction for the SME. With no measurement, the best estimate of the SME composition is the same as the predicted measurement. The contents are concentrated (i.e., water transferred to the SMECT) until the SME volume equals 6500.0 gallons:

New Transfer Data for SME to SMECT Transfer			
Information for Source Vessel SME Batch 2			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	0.9-1.5		: 1.2615
Volume Transferred from Source Tank	0-10000	Gal	: 2006.7
Information for Target Vessel SMECT Batch 1			
<i>Item</i>	<i>Range</i>	<i>Units</i>	<i>Value</i>
Target Tank Material Initial Specific Gravity	0.9-1.1		: 1.0
Target Tank Initial Volume	0-10000	Gal	: 0.
Target Tank Material Final Specific Gravity	0.9-1.1		: 1.0
Target Tank Final Volume	0-10000	Gal	: 2006.7
<i>Operations</i>			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

Processing for SME Batch 2 is now complete. The final step is to sample the SME material and test the composition for acceptability. The SME analysis is entered into the PCCS using the Data Entry Display. The "Enter New Analysis" command is selected and the SME is chosen as the vessel. The following data are entered:

New Sample Analysis for SME			
Sample Analysis for SME in WT%-OXIDES			
Item	Range	Units	Value
Sample-ID			: Sample4705
Wgt% Solids	38.0-47.0		: 45.6
Calcined Wgt% Solids	0.0-47.0		: 40.7
Specific Gravity	1.2-1.5		: 1.35
AL	0.0-50.0	Wt%	: 2.55
B	0.0-50.0	Wt%	: 2.2
CA	0.0-50.0	Wt%	: 0.9
FE	0.0-50.0	Wt%	: 9.0
K	0.0-50.0	Wt%	: 1.95
LI	0.0-50.0	Wt%	: 2.15
MG	0.0-50.0	Wt%	: 0.85
MN	0.0-50.0	Wt%	: 1.65
NA	0.0-50.0	Wt%	: 5.85
NI	0.0-50.0	Wt%	: 0.6
SI	0.0-50.0	Wt%	: 24.35
TI	0.0-50.0	Wt%	: 0.20
U	0.0-50.0	Wt%	: 0.45
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

After the sample measurement is entered, the SME contains 6500.0 gallons of material with the measured, predicted and best compositions as shown in the Detailed Display for SME Batch 2.

From the Batching Display, the "Determine SME Acceptability" command is selected, and the right-hand window summarizes the relevant acceptability information for the target composition. The information computed for the Property and Measurement Acceptability tests can be presented by clicking the middle mouse button on the Acceptability Titles to show all output fields. Since the PCCS indicates that this material possesses acceptable predicted properties, 5000.0 gallons of acceptable melter feed material can be transferred to the MFT. From the Data Entry Display, the "Enter New Transfer" command is selected for the SME to MFT transfer. The following information is entered:

New Transfer Data for SME to MFT Transfer			
Information for Source Vessel SME Batch 2			
Item	Range	Units	Value
Transfer-ID			: TRNSFR2168
Source Material Specific Gravity	1.2-1.5		: 1.35
Volume Transferred from Source Tank	4500-7000	Gal	: 5000.0
Information for Target Vessel MFT Batch 1			
Item	Range	Units	Value
Target Tank Material Initial Specific Gravity	1.2-1.5		: 1.35
Target Tank Initial Volume	0-1800	Gal	: 5000.0
Target Tank Material Final Specific Gravity	1.2-1.5		: 1.35
Target Tank Final Volume	4500-7000	Gal	: 10000.0
Operations			
Select for Supervisor Permissive to Override Data Ranges			
Done		Abort	

This concludes the SME Batch 2 cycle. A new SME Batch is now commenced by choosing the "Start New Batch" command from the Data Entry Display and confirming. Now the any subsequent SRAT and SME batches can be processed using the PCCS.

8.0 Conclusions

This test case will be used to illustrate the major control functions of the PCCS including targeting, monitoring, and remediation. Remediation will be demonstrated by induction; that is, the remediation algorithm utilizes the same internal functions used by the SRAT and SME targeting algorithms. Therefore, if the SRAT and SME targeting algorithms are validated, the remediation algorithms can be assumed valid. The monitoring algorithm will also be proven using this input information.

The final validation will concern the statistics involved in performing the PCCS operations. The Maximum A Posteriori (MAP) estimates of the compositions in the DWPF process vessels will be computed as well as the appropriate covariance matrices. The MAP estimate is the best possible estimate based on both projected and measured compositions weighted by their respective covariance matrices. All important parameters will be computed independently and compared to PCCS predicted values.

Appendix A
Normalized Molar Oxide Covariance Matrices

The SRAT normalized molar oxide covariance matrix representing the oxides: Al₂O₃, BaO, B₂O₃, CaO, CuO, Fe₂O₃, MgO, MnO, NiO, TiO₂, K₂O, and Na₂O is

3.46E+00	4.85E-03	-2.49E+00	-4.75E-01	-4.03E-02	4.16E-01	-6.00E-02	2.27E-01	6.98E-02
4.85E-03	5.73E-05	-1.37E-02	-1.09E-03	1.29E-05	5.62E-03	-9.22E-05	3.59E-03	7.24E-04
-2.49E+00	-1.37E-02	4.25E+00	3.11E-01	-3.44E-03	-1.30E+00	2.14E-02	-8.25E-01	-1.79E-01
-4.75E-01	-1.09E-03	3.11E-01	1.06E-01	1.07E-02	-1.02E-01	1.55E-02	-5.78E-02	-1.39E-02
-4.03E-02	1.29E-05	-3.44E-03	1.07E-02	1.52E-03	2.45E-03	1.85E-03	2.07E-03	2.90E-04
4.16E-01	5.62E-03	-1.30E+00	-1.02E-01	2.45E-03	5.67E-01	-8.35E-03	3.56E-01	7.18E-02
-6.00E-02	-9.22E-05	2.14E-02	1.55E-02	1.85E-03	-8.35E-03	2.50E-03	-4.26E-03	-1.07E-03
2.27E-01	3.59E-03	-8.25E-01	-5.78E-02	2.07E-03	3.56E-01	-4.26E-03	2.27E-01	4.51E-02
6.98E-02	7.24E-04	-1.79E-01	-1.39E-02	2.90E-04	7.18E-02	-1.07E-03	4.51E-02	9.43E-03
-1.66E-02	-4.35E-05	-6.01E-04	7.68E-03	1.04E-03	-3.59E-03	1.35E-03	-2.15E-03	-3.67E-04
-1.84E-01	3.69E-04	-2.81E-02	2.95E-02	4.37E-03	3.54E-02	4.97E-03	2.70E-02	4.37E-03
-9.17E-01	-3.19E-04	2.54E-01	1.71E-01	1.94E-02	-3.68E-02	2.62E-02	9.35E-04	-7.32E-03
						-1.66E-02	-1.84E-01	-9.17E-01
						-4.35E-05	3.69E-04	-3.19E-04
						-6.01E-04	-2.81E-02	2.54E-01
						7.68E-03	2.95E-02	1.71E-01
						1.04E-03	4.37E-03	1.94E-02
						-3.59E-03	3.54E-02	-3.68E-02
						1.35E-03	4.97E-03	2.62E-02
						-2.15E-03	2.70E-02	9.35E-04
						-3.67E-04	4.37E-03	-7.32E-03
						8.93E-04	1.82E-03	1.06E-02
						1.82E-03	2.28E-02	8.15E-02
						1.06E-02	8.15E-02	3.98E-01

The PFSFT normalized molar oxide covariance matrix representing the oxides: SiO₂, B₂O₃, Li₂O, MgO, and Na₂O is

0.16165155	0.03170132	-0.0746364	-0.0621265	-0.0565897
0.03170132	0.0255338	-0.023772	-0.0272181	-0.0062449
-0.0746364	-0.023772	0.0562779	0.04155677	5.74E-04
-0.0621265	-0.0272181	0.04155677	0.05407548	-0.0062878
-0.0565897	-0.0062449	5.74E-04	-0.0062878	0.06854856

The Tank-51 normalized molar oxide covariance matrix representing the elements: Al₂O₃, B₂O₃, BaO, CaO, Cr₂O₃, CuO, Fe₂O₃, Li₂O, MgO, MnO, Na₂O, NiO, P₂O₅, SiO₂, and TiO₂ is

6.73E-01	9.20E-04	1.16E-02	-1.96E-02	-5.10E-03	-6.89E-03	-4.26E-01	3.39E-03	-3.00E-02
9.20E-04	1.46E-04	1.85E-05	-7.07E-04	1.22E-06	-2.38E-05	-7.63E-04	1.32E-05	1.25E-04
1.16E-02	1.85E-05	2.15E-04	-3.41E-04	-1.72E-04	-1.04E-04	-6.95E-03	6.38E-05	-4.83E-04
-1.96E-02	-7.07E-04	-3.41E-04	9.83E-02	6.42E-05	1.73E-03	1.54E-02	3.03E-04	1.61E-02
-5.10E-03	1.22E-06	-1.72E-04	6.42E-05	2.42E-03	-1.73E-04	-7.97E-03	-2.09E-04	-9.06E-04
-6.89E-03	-2.38E-05	-1.04E-04	1.73E-03	-1.73E-04	3.73E-04	9.05E-03	1.75E-05	1.46E-04
-4.26E-01	-7.63E-04	-6.95E-03	1.54E-02	-7.97E-03	9.05E-03	6.98E-01	-1.88E-03	1.39E-02
3.39E-03	1.32E-05	6.38E-05	3.03E-04	-2.09E-04	1.75E-05	-1.88E-03	1.51E-04	-4.82E-05
-3.00E-02	1.25E-04	-4.83E-04	1.61E-02	-9.06E-04	1.46E-04	1.39E-02	-4.82E-05	2.11E-02
-1.65E-01	-3.88E-04	-2.61E-03	1.57E-02	-4.16E-03	4.35E-03	3.00E-01	-4.47E-04	4.42E-03
-6.92E-01	-6.25E-04	-1.31E-02	-1.37E-01	2.71E-02	-6.32E-03	-2.87E-01	-5.25E-03	-4.03E-03
-6.91E-02	-1.24E-04	-1.12E-03	2.08E-03	-1.24E-03	1.71E-03	1.20E-01	-2.15E-04	1.61E-03
8.62E-04	-1.72E-05	4.09E-05	1.48E-03	-4.33E-04	1.75E-04	5.28E-03	1.20E-04	-6.11E-05
7.23E-01	1.43E-03	1.30E-02	5.99E-03	-9.12E-03	-4.13E-03	-4.33E-01	3.96E-03	-2.20E-02
-5.11E-04	-6.32E-06	4.74E-06	8.01E-04	-8.82E-05	8.38E-05	1.57E-03	3.62E-05	1.07E-04
			-1.65E-01	-6.92E-01	-6.91E-02	8.62E-04	7.23E-01	-5.11E-04
			-3.88E-04	-6.25E-04	-1.24E-04	-1.72E-05	1.43E-03	-6.32E-06
			-2.61E-03	-1.31E-02	-1.12E-03	4.09E-05	1.30E-02	4.74E-06
			1.57E-02	-1.37E-01	2.08E-03	1.48E-03	5.99E-03	8.01E-04
			-4.16E-03	2.71E-02	-1.24E-03	-4.33E-04	-9.12E-03	-8.82E-05
			4.35E-03	-6.32E-03	1.71E-03	1.75E-04	-4.13E-03	8.38E-05
			3.00E-01	-2.87E-01	1.20E-01	5.28E-03	-4.33E-01	1.57E-03
			-4.47E-04	-5.25E-03	-2.15E-04	1.20E-04	3.96E-03	3.62E-05
			4.42E-03	-4.03E-03	1.61E-03	-6.11E-05	-2.20E-02	1.07E-04
			1.35E-01	-1.85E-01	5.27E-02	3.08E-03	-1.59E-01	9.12E-04
			-1.85E-01	2.38E+00	-6.21E-02	-1.64E-02	-9.90E-01	-4.41E-03
			5.27E-02	-6.21E-02	2.15E-02	1.14E-03	-6.74E-02	3.78E-04
			3.08E-03	-1.64E-02	1.14E-03	4.99E-04	4.14E-03	1.09E-04
			-1.59E-01	-9.90E-01	-6.74E-02	4.14E-03	9.33E-01	9.55E-04
			9.12E-04	-4.41E-03	3.78E-04	1.09E-04	9.55E-04	6.23E-05

The PRBT normalized molar oxide covariance matrix representing the oxides: Al₂O₃, B₂O₃, BaO, CaO, Cr₂O₃, Cs₂O, CuO, Fe₂O₃, K₂O, Li₂O, MgO, MnO, Na₂O, NiO, P₂O₅, SiO₂, and TiO₂ is

4.02E-05	4.08E-03	3.93E-07	4.26E-05	1.77E-06	2.05E-04	4.12E-05	-8.41E-04	-4.77E-03
4.08E-03	5.64E-01	2.44E-05	6.11E-03	1.48E-04	2.80E-02	3.40E-03	-1.04E-01	-5.18E-01
3.93E-07	2.44E-05	1.66E-08	9.72E-07	3.40E-08	-6.16E-07	1.55E-07	2.05E-05	-1.02E-04
4.26E-05	6.11E-03	9.72E-07	1.50E-04	1.90E-06	1.95E-04	9.02E-06	8.29E-04	-1.23E-02
1.77E-06	1.48E-04	3.40E-08	1.90E-06	1.22E-07	4.68E-06	1.66E-06	5.73E-07	-2.03E-04
2.05E-04	2.80E-02	-6.16E-07	1.95E-04	4.68E-06	2.12E-03	1.87E-04	-9.06E-03	-1.45E-02
4.12E-05	3.40E-03	1.55E-07	9.02E-06	1.66E-06	1.87E-04	3.90E-04	-1.37E-03	-1.67E-02
-8.41E-04	-1.04E-01	2.05E-05	8.29E-04	5.73E-07	-9.06E-03	-1.37E-03	9.51E-02	-5.32E-02
-4.77E-03	-5.18E-01	-1.02E-04	-1.23E-02	-2.03E-04	-1.45E-02	-1.67E-02	-5.32E-02	2.45E+00
3.58E-06	7.15E-05	2.02E-07	7.08E-06	4.82E-07	-1.77E-05	9.97E-07	3.28E-04	-6.31E-04
1.93E-05	2.73E-03	4.66E-07	7.42E-05	6.23E-07	7.72E-05	2.48E-05	3.99E-04	-8.03E-03
2.06E-05	3.62E-03	1.56E-06	1.68E-04	1.77E-06	-5.94E-05	-2.71E-06	3.42E-03	-1.66E-02
9.25E-04	-9.55E-03	4.86E-05	4.36E-03	2.89E-05	-7.73E-03	1.39E-02	6.90E-02	-1.76E+00
2.32E-05	2.76E-03	2.10E-07	3.61E-05	7.52E-07	1.46E-04	2.55E-05	-4.56E-04	-3.70E-03
1.38E-06	1.07E-04	3.61E-08	2.85E-06	8.53E-08	1.63E-06	-7.35E-07	2.80E-05	-3.19E-04
2.12E-04	1.64E-02	4.68E-06	3.18E-04	1.21E-05	3.88E-04	1.93E-04	-1.56E-05	-3.63E-02
1.95E-08	-2.23E-05	1.03E-08	2.42E-08	2.46E-08	-2.49E-06	5.16E-07	2.60E-05	-3.94E-05
3.58E-06	1.93E-05	2.06E-05	9.25E-04	2.32E-05	1.38E-06	2.12E-04	1.95E-08	
7.15E-05	2.73E-03	3.62E-03	-9.55E-03	2.76E-03	1.07E-04	1.64E-02	-2.23E-05	
2.02E-07	4.66E-07	1.56E-06	4.86E-05	2.10E-07	3.61E-08	4.68E-06	1.03E-08	
7.08E-06	7.42E-05	1.68E-04	4.36E-03	3.61E-05	2.85E-06	3.18E-04	2.42E-08	
4.82E-07	6.23E-07	1.77E-06	2.89E-05	7.52E-07	8.53E-08	1.21E-05	2.46E-08	
-1.77E-05	7.72E-05	-5.94E-05	-7.73E-03	1.46E-04	1.63E-06	3.88E-04	-2.49E-06	
9.97E-07	2.48E-05	-2.71E-06	1.39E-02	2.55E-05	-7.35E-07	1.93E-04	5.16E-07	
3.28E-04	3.99E-04	3.42E-03	6.90E-02	-4.56E-04	2.80E-05	-1.56E-05	2.60E-05	
-6.31E-04	-8.03E-03	-1.66E-02	-1.76E+00	-3.70E-03	-3.19E-04	-3.63E-02	-3.94E-05	
3.29E-06	1.69E-06	1.47E-05	1.73E-04	4.98E-07	4.20E-07	4.42E-05	2.08E-07	
1.69E-06	4.46E-05	9.34E-05	4.38E-03	2.00E-05	1.28E-06	1.67E-04	-7.87E-08	
1.47E-05	9.34E-05	2.86E-04	8.64E-03	2.82E-05	3.49E-06	3.19E-04	6.89E-07	
1.73E-04	4.38E-03	8.64E-03	1.66E+00	9.77E-04	1.61E-04	1.60E-02	3.56E-05	
4.98E-07	2.00E-05	2.82E-05	9.77E-04	1.78E-05	6.80E-07	1.21E-04	-1.37E-07	
4.20E-07	1.28E-06	3.49E-06	1.61E-04	6.80E-07	3.67E-07	1.08E-05	2.48E-08	
4.42E-05	1.67E-04	3.19E-04	1.60E-02	1.21E-04	1.08E-05	2.07E-03	1.30E-06	
2.08E-07	-7.87E-08	6.89E-07	3.56E-05	-1.37E-07	2.48E-08	1.30E-06	1.88E-08	

Appendix B
Elemental Oxide Covariance Matrices

The SRAT elemental covarinace matrix representing the elements: Al, Ba, B, Ca, Cu, Fe, Mg, Mn, Nd, Ni, Ru, Sr, Ti, Zn, K, and Na is

2.62E-01	1.65E-03	-5.41E-02	-1.73E-02	-2.12E-03	1.27E-01	-1.19E-03	3.78E-02
1.65E-03	2.51E-05	-7.66E-04	-1.90E-04	-1.31E-05	2.03E-03	-1.30E-05	6.20E-04
-5.41E-02	-7.66E-04	3.95E-02	5.47E-03	-6.55E-05	-5.92E-02	2.41E-04	-1.84E-02
-1.73E-02	-1.90E-04	5.47E-03	2.10E-03	2.74E-04	-1.46E-02	1.68E-04	-4.51E-03
-2.12E-03	-1.31E-05	-6.55E-05	2.74E-04	6.60E-05	-8.52E-04	2.87E-05	-2.86E-04
1.27E-01	2.03E-03	-5.92E-02	-1.46E-02	-8.52E-04	1.68E-01	-9.80E-04	5.06E-02
-1.19E-03	-1.30E-05	2.41E-04	1.68E-04	2.87E-05	-9.80E-04	1.54E-05	-3.07E-04
3.78E-02	6.20E-04	-1.84E-02	-4.51E-03	-2.86E-04	5.06E-02	-3.07E-04	1.54E-02
1.46E-02	1.78E-04	-8.53E-03	-1.50E-03	-7.31E-05	1.31E-02	-8.19E-05	4.22E-03
9.21E-03	1.36E-04	-4.30E-03	-9.92E-04	-5.37E-05	1.11E-02	-6.37E-05	3.36E-03
6.98E-03	4.51E-05	-1.82E-03	-5.31E-04	-6.46E-05	3.40E-03	-3.79E-05	1.04E-03
-2.40E-03	-2.43E-05	7.82E-04	3.40E-04	5.86E-05	-1.58E-03	3.00E-05	-5.46E-04
-3.17E-04	-1.03E-05	1.81E-05	1.65E-04	3.59E-05	-7.23E-04	1.79E-05	-2.47E-04
2.83E-04	6.43E-06	-2.70E-04	-3.01E-05	2.00E-06	5.19E-04	-1.00E-06	1.66E-04
-9.49E-03	1.00E-05	-7.43E-04	2.77E-04	1.02E-04	9.02E-04	2.57E-05	3.34E-04
-7.09E-03	-9.13E-05	6.65E-03	7.85E-04	-3.21E-05	-6.47E-03	2.57E-05	-2.04E-03

1.46E-02	9.21E-03	6.98E-03	-2.40E-03	-3.17E-04	2.83E-04	-9.49E-03	-7.09E-03
1.78E-04	1.36E-04	4.51E-05	-2.43E-05	-1.03E-05	6.43E-06	1.00E-05	-9.13E-05
-8.53E-03	-4.30E-03	-1.82E-03	7.82E-04	1.81E-05	-2.70E-04	-7.43E-04	6.65E-03
-1.50E-03	-9.92E-04	-5.31E-04	3.40E-04	1.65E-04	-3.01E-05	2.77E-04	7.85E-04
-7.31E-05	-5.37E-05	-6.46E-05	5.86E-05	3.59E-05	2.00E-06	1.02E-04	-3.21E-05
1.31E-02	1.11E-02	3.40E-03	-1.58E-03	-7.23E-04	5.19E-04	9.02E-04	-6.47E-03
-8.19E-05	-6.37E-05	-3.79E-05	3.00E-05	1.79E-05	-1.00E-06	2.57E-05	2.57E-05
4.22E-03	3.36E-03	1.04E-03	-5.46E-04	-2.47E-04	1.66E-04	3.34E-04	-2.04E-03
2.14E-03	9.83E-04	4.44E-04	-2.66E-04	-4.90E-05	6.01E-05	5.20E-05	-1.46E-03
9.83E-04	7.58E-04	2.36E-04	-1.13E-04	-4.21E-05	3.37E-05	6.86E-05	-5.52E-04
4.44E-04	2.36E-04	2.27E-04	-8.39E-05	-1.62E-05	1.04E-05	-2.87E-04	-2.46E-04
-2.66E-04	-1.13E-04	-8.39E-05	7.86E-05	3.68E-05	-4.29E-06	3.93E-05	1.30E-04
-4.90E-05	-4.21E-05	-1.62E-05	3.68E-05	2.83E-05	-2.21E-12	-1.52E-05	-8.64E-06
6.01E-05	3.37E-05	1.04E-05	-4.29E-06	-2.21E-12	3.43E-06	5.71E-06	-2.67E-05
5.20E-05	6.86E-05	-2.87E-04	3.93E-05	-1.52E-05	5.71E-06	8.70E-04	-2.66E-04
-1.46E-03	-5.52E-04	-2.46E-04	1.30E-04	-8.64E-06	-2.67E-05	-2.66E-04	1.46E-03

The PFSFT elemental covariance matrix for the elements: Si, B, Li, Mg, and Na is

1.0036712	0.05921529	0.06411682	0.04276056	-0.039101
0.05921529	0.00663138	0.00170298	-0.00125	-0.0036421
0.06411682	0.00170298	0.00891225	0.00894868	-0.0023623
0.04276056	-0.00125	0.00894868	0.01279406	2.28E-04
-0.039101	-0.0036421	-0.0023623	2.28E-04	0.02745317

The Tank-51 elemental covariance matrix representing the elements: Al, B, Ba, Ca, Cr, Cu, Fe, Li, Mg, Mn, Na, Ni, P, Si, and Ti is

8.76E-02	2.19E-05	3.81E-03	3.82E-03	-2.12E-03	-1.85E-04	1.37E-02	6.17E-05	-7.09E-04
2.19E-05	3.40E-06	1.33E-06	-3.28E-05	-6.38E-07	-1.68E-06	-9.44E-05	1.53E-07	3.42E-06
3.81E-03	1.33E-06	1.80E-04	1.65E-04	-1.54E-04	-1.41E-06	8.85E-04	3.20E-06	-2.45E-05
3.82E-03	-3.28E-05	1.65E-04	1.19E-02	-5.45E-05	7.29E-04	6.90E-02	-2.80E-06	1.35E-03
-2.12E-03	-6.38E-07	-1.54E-04	-5.45E-05	1.32E-03	-6.62E-05	-5.38E-03	-1.60E-05	-1.21E-04
-1.85E-04	-1.68E-06	-1.41E-06	7.29E-04	-6.62E-05	1.43E-04	1.20E-02	-3.81E-07	7.58E-05
1.37E-02	-9.44E-05	8.85E-04	6.90E-02	-5.38E-03	1.20E-02	1.60E+00	-3.04E-04	1.03E-02
6.17E-05	1.53E-07	3.20E-06	-2.80E-06	-1.60E-05	-3.81E-07	-3.04E-04	1.43E-06	-1.58E-06
-7.09E-04	3.42E-06	-2.45E-05	1.35E-03	-1.21E-04	7.58E-05	1.03E-02	-1.58E-06	7.23E-04
5.08E-03	-2.50E-05	3.06E-04	1.60E-02	-1.39E-03	2.68E-03	3.48E-01	-5.37E-05	2.16E-03
-7.23E-02	-4.03E-05	-3.59E-03	-2.76E-03	6.42E-03	5.41E-04	1.26E-01	-2.14E-04	1.31E-03
1.36E-03	-8.30E-06	8.86E-05	6.03E-03	-4.52E-04	1.10E-03	1.43E-01	-2.30E-05	8.63E-04
3.25E-04	-1.28E-06	2.58E-05	3.53E-04	-1.47E-04	5.77E-05	4.84E-03	4.70E-06	1.95E-05
4.83E-02	2.53E-05	2.21E-03	3.83E-03	-1.74E-03	2.05E-04	1.22E-02	4.05E-05	-9.99E-06
4.24E-05	-2.84E-07	6.45E-06	1.23E-04	-2.20E-05	1.81E-05	1.08E-03	1.20E-06	1.15E-05
5.08E-03	-7.23E-02	1.36E-03	3.25E-04	4.83E-02	4.24E-05			
-2.50E-05	-4.03E-05	-8.30E-06	-1.28E-06	2.53E-05	-2.84E-07			
3.06E-04	-3.59E-03	8.86E-05	2.58E-05	2.21E-03	6.45E-06			
1.60E-02	-2.76E-03	6.03E-03	3.53E-04	3.83E-03	1.23E-04			
-1.39E-03	6.42E-03	-4.52E-04	-1.47E-04	-1.74E-03	-2.20E-05			
2.68E-03	5.41E-04	1.10E-03	5.77E-05	2.05E-04	1.81E-05			
3.48E-01	1.26E-01	1.43E-01	4.84E-03	1.22E-02	1.08E-03			
-5.37E-05	-2.14E-04	-2.30E-05	4.70E-06	4.05E-05	1.20E-06			
2.16E-03	1.31E-03	8.63E-04	1.95E-05	-9.99E-06	1.15E-05			
7.63E-02	1.96E-02	3.12E-02	1.18E-03	4.33E-03	2.65E-04			
1.96E-02	2.94E-01	9.19E-03	-1.94E-03	-5.73E-02	-3.86E-04			
3.12E-02	9.19E-03	1.29E-02	4.72E-04	1.40E-03	1.12E-04			
1.18E-03	-1.94E-03	4.72E-04	1.05E-04	4.74E-04	1.84E-05			
4.33E-03	-5.73E-02	1.40E-03	4.74E-04	3.30E-02	1.32E-04			
2.65E-04	-3.86E-04	1.12E-04	1.84E-05	1.32E-04	7.71E-06			

The PRBT elemental covariance matrix representing the elements: Al, B, Ba, Ca, Cr, Cs, Cu, Fe, K, Li, Mg, Mn, Na, Ni, P, Si, and Ti is

9.31E-01	3.76E+01	2.92E-02	7.61E-01	8.51E-02	5.34E+00	2.44E+00	-3.00E+01	-4.74E+01
3.76E+01	2.07E+03	1.02E+00	4.45E+01	3.10E+00	2.86E+02	-1.12E+01	-1.21E+03	1.30E+03
2.92E-02	1.02E+00	2.91E-03	5.77E-02	4.36E-03	1.55E-02	5.36E-02	3.00E+00	-3.96E+00
7.61E-01	4.45E+01	5.77E-02	2.10E+00	7.79E-02	3.80E+00	-3.43E+00	5.58E+01	-6.07E+01
8.51E-02	3.10E+00	4.36E-03	7.79E-02	1.11E-02	3.05E-01	3.36E-01	6.49E-01	-6.37E+00
5.34E+00	2.86E+02	1.55E-02	3.80E+00	3.05E-01	6.27E+01	-2.94E+00	-4.02E+02	6.01E+02
2.44E+00	-1.12E+01	5.36E-02	-3.43E+00	3.36E-01	-2.94E+00	1.65E+02	-2.01E+02	-1.80E+03
-3.00E+01	-1.21E+03	3.00E+00	5.58E+01	6.49E-01	-4.02E+02	-2.01E+02	9.95E+03	-7.82E+02
-4.74E+01	1.30E+03	-3.96E+00	-6.07E+01	-6.37E+00	6.01E+02	-1.80E+03	-7.82E+02	1.65E+05
2.94E-02	7.69E-01	3.44E-03	5.00E-02	6.04E-03	-3.97E-02	1.06E-01	4.39E+00	-2.38E+00
2.05E-01	1.17E+01	1.74E-02	6.27E-01	1.73E-02	8.12E-01	-2.60E-01	1.77E+01	-3.77E+01
6.87E-01	4.97E+01	1.26E-01	3.65E+00	1.14E-01	-3.61E-01	-5.64E+00	2.19E+02	-1.05E+02
4.79E+00	-1.04E+03	3.31E+00	4.89E+01	1.52E+00	-3.73E+02	8.14E+02	5.13E+03	-3.16E+04
6.01E-01	2.88E+01	2.10E-02	7.55E-01	4.44E-02	4.22E+00	8.20E-01	-1.12E+01	-6.52E+00
3.91E-02	1.31E+00	2.72E-03	6.28E-02	4.67E-03	7.20E-02	-1.23E-01	1.93E+00	-8.80E+00
2.91E+00	1.05E+02	1.62E-01	3.62E+00	3.06E-01	9.19E+00	1.30E+01	1.50E+01	-4.39E+02
1.87E-03	-7.63E-02	6.01E-04	3.78E-03	1.06E-03	-4.52E-02	7.19E-02	1.16E+00	-8.77E-01
2.94E-02	2.05E-01	6.87E-01	4.79E+00	6.01E-01	3.91E-02	2.91E+00	1.87E-03	
7.69E-01	1.17E+01	4.97E+01	-1.04E+03	2.88E+01	1.31E+00	1.05E+02	-7.63E-02	
3.44E-03	1.74E-02	1.26E-01	3.31E+00	2.10E-02	2.72E-03	1.62E-01	6.01E-04	
5.00E-02	6.27E-01	3.65E+00	4.89E+01	7.55E-01	6.28E-02	3.62E+00	3.78E-03	
6.04E-03	1.73E-02	1.14E-01	1.52E+00	4.44E-02	4.67E-03	3.06E-01	1.06E-03	
-3.97E-02	8.12E-01	-3.61E-01	-3.73E+02	4.22E+00	7.20E-02	9.19E+00	-4.52E-02	
1.06E-01	-2.60E-01	-5.64E+00	8.14E+02	8.20E-01	-1.23E-01	1.30E+01	7.19E-02	
4.39E+00	1.77E+01	2.19E+02	5.13E+03	-1.12E+01	1.93E+00	1.50E+01	1.16E+00	
-2.38E+00	-3.77E+01	-1.05E+02	-3.16E+04	-6.52E+00	-8.80E+00	-4.39E+02	-8.77E-01	
5.33E-03	1.09E-02	1.26E-01	2.33E+00	1.27E-02	3.17E-03	1.51E-01	1.15E-03	
1.09E-02	2.23E-01	1.21E+00	3.31E+01	2.47E-01	1.76E-02	1.17E+00	4.53E-04	
1.26E-01	1.21E+00	8.79E+00	1.82E+02	1.04E+00	1.12E-01	5.48E+00	2.10E-02	
2.33E+00	3.31E+01	1.82E+02	2.48E+04	1.03E+01	4.01E+00	2.12E+02	9.48E-01	
1.27E-02	2.47E-01	1.04E+00	1.03E+01	5.24E-01	2.31E-02	2.01E+00	-1.39E-03	
3.17E-03	1.76E-02	1.12E-01	4.01E+00	2.31E-02	1.13E-02	1.63E-01	6.41E-04	
1.51E-01	1.17E+00	5.48E+00	2.12E+02	2.01E+00	1.63E-01	1.38E+01	1.59E-02	
1.15E-03	4.53E-04	2.10E-02	9.48E-01	-1.39E-03	6.41E-04	1.59E-02	3.52E-04	

**DATE
FILMED**

4 / 20 / 93