Final Report
DE FG02 84ER13218
Theta Pinch Discharges for Solids Vaporization and Elemental Chemical Analysis
Alexander Scheeline

Scientific Accomplishments

DOE/ER/13218--29

1. Echelle Spectrometry

DE93 013228

We have completed development of our locally-designed echelle spectrometer by completing software, written in Microsoft Professional BASIC 7.0, to convert charge-coupled device (CCD) detected spectral images into useful information. Raw spectra are compensated for wavelength-dependent system throughput, coma, and continuum, lines resolution is numerically improved, and raw data are interpreted either in terms of concentration or to provide diagnostics of electron concentration or species excitation. Details are provided in several publications, both in press and in print. Approximately half the effort in the last year has focused on finishing this software and writing the work up for publication. As described in the book chapter by C. A. Bye (and further detailed in her thesis and, potentially, in additional papers), the broad simultaneously sensed wavelength range provided by the echelle permits some unique excitation measurements to be made. While this development is not directly the purpose towards which the grant was directed, its successful completion now allows very rapid data collection and interpretation.

2. Analysis of Refractories

The main motivation for studying the theta pinch has been the development of analytical methods for the metallic components of refractory insulating solids. Z. Wang's work, recently published, shows that powdered samples can in fact be accurately assayed if adequate internal standards are available. The simultaneous observation characteristics of the echelle/CCD are essential for providing meaningful data. Mixed powdered oxides of Al, Mn, Mg, and Ti showed linear response for >0.5% weight of minor constituents. Because light emission from the pinch was time-integrated, continuum limited detection to only major and minor components. Data indicate detection limits on the order of 0.1% for these elements as oxides. For comparison, after dissolution in ordinary acidic aqueous solution, this corresponds to a concentration of roughly 10 ppm, so that this technique is competitive with X-ray fluorescence, for example. Higher throughput combined with time gating might reasonably lower the detection limits by 2 orders of magnitude. One must compare such performance against RF glow discharge mass spectrometry, as championed by R. K. Marcus of Clemson University; detection limits are already better for his techniques than the best one can extrapolate for the theta pinch, absent mass spectrometric detection. Thus, we must conclude that the theta pinch, when used to assay powders, is better than a DC arc (since no conducting buffer is required, so the operating detection limits are better, as is the precision), but not good enough to be commercially competitive.

In unpublished work, we studied the effect of powder size on signal. Coarse grinding (most particles > 10 μ m in diameter) or very fine grinding (typical particles < 1 μ m diameter) gave better S/N than intermediate amounts of grinding. From this we conclude that fine powders are vaporized completely, dusts on the surface of coarse powders are usefully sampled, but that intermediate-sized particles are only partially sampled, providing poor precision.

3. Powder vs. Bulk Sampling

The effect of particle size on analytical signal hints at the crux of the theta pinch development question: can the pinch plasma in fact sample bulk solids in a matrix-independent

manner, providing signals from each element proportional to their concentration in the original matrix? For alumina materials, we have found that repeated pinch firing leads to exponentially decaying emission intensity on successive firings. Thus, after 10 pinches, an alumina sample that initially gave entirely adequate emission gives no detectable emission above background. The sample surface has melted and flowed so that, in place of the original rough, sintered surface one finds a smooth, polished surface. Apparently, the early signals comes from dusts, small projections, and surface roughness, not from uniform sampling of surface material. The critical question then is: is the lack of late sampling due to the formation of a space charge, preventing intimate contact between the vaporizing plasma and the specimen, or is it due to low heat capacity and thermal conductivity of the plasma compared to high heat capacity and thermal conductivity of the sample? If the former is the case, an RF pinch could in principle be designed to sample bulk solids, by collapsing the space charge repeatedly, permitting ion bombardment by the plasma. If the latter is the case, no low pressure plasma can thermally sample bulk solids, and only the sputtering of a glow discharge can directly sample such materials. We reached the point of designing an experiment to ask this crucial question just as funds for the grant expired.

4. Definitive Sampling Limitation Studies

We are, however, continuing the work using equipment obtained under the grant to pursue this matter to its logical conclusion. We are using a streak camera/space-resolving, line-width measurement approach to working on the problem. If heat transfer is the limiting factor in sampling, the analyte surface will quench the plasma, leading to NARROW spectral lines adjacent to the sample. Furthermore, when the shock wave from the plasma impinges on the sample surface, whatever spectral lines still are emitted will suddenly narrow compared to their widths only a few hundred nanoseconds (and a few millimeters) away. On the other hand, if a space charge causes the limitations to sampling, plasma emission lines will BROADEN as the space charge builds up, and will increase in width AFTER the plasma encounters the sample. We are currently making final preparations for these experiments. Following their completion, D. L. Miller will complete his thesis work, and appropriate papers will be written.

Personnel

Five individuals have received RA support from this grant:

Cheryl A. Bye	Ph.D. anticipated, summer, 1993. Worked on development of echelle spectrometer, used for some pinch data collection experiments.
Angela Kovacs-Boerger	M.S. in the Teaching of Chemistry anticipated, summer, 1993. Involved in instrument development.
Duane L. Miller	Ph.D. anticipated, summer, 1993. Worked on spectral reduction software, instrument development, and was main worker involved in data collection on plasma dynamics and plasma/surface interactions.
Dean L. Olson	Ph.D. anticipated, fall, 1993. Worked on instrument development and data collection.
Zuwei Wang	Research associate. Worked on quantitative analysis of powders; work resulted in one published article. Now a graduate student at Mississippi State University.

Publications

1. Alexander Scheeline, C. A. Bye, D. L. Miller, S. W. Rynders, and R. C. Owen, Jr., "Design and Characterization of an Echelle Spectrometer for Fundamental and Applied Emission Spectrochemical Analysis", *Appl. Spectrosc.*, **45**, 334 (1991).
2. Zuwei Wang and Alexander Scheeline, "Study of Internal Standardization for Analysis of Powdered Samples Using a Theta Pinch Discharge", *J. Anal. Atomic Spectrosc.*, **6**, 553 (1991).
3. Alexander Scheeline, "Automated Spectrography and Plasma Diagnostics", *Intelligent Instruments and Computers*, in press (1993).
4. C. A. Bye and A. Scheeline, "Two-Dimensional Array Detectors for Plasma Diagnostics", in *The Applications of Charge Transfer Devices in Chemistry*, J. V. Sweedler, K. Ratzlaff, and M. B. Denton ed. (VCH, New York, 1993, in press).
5. D. L. Miller and A. Scheeline, "A Computer Program for the Collection, Reduction, and Analysis of Echelle Spectra", *Spectrochim. Acta* **48B**, in press (1993).

Oral Presentations

1. "Particle Size Effects on Ceramic Analysis Using a Theta Pinch Discharge," A. Scheeline and D. L. Miller, FACSS/Pacific Conference, Anaheim, CA (October, 1991).
2. Aspects of Quantitation with a Theta Pinch Emission Source, A. Scheeline and D.L. Miller, VACSS XIX, Philadelphia, PA (September, 1992).

Planned Manuscripts

These manuscripts are not yet written, and are listed as an indication of what we believe will be the result of our current efforts.

1. D. L. Miller and A. Scheeline, "Fundamental Limitations to Argon Theta Pinch Sampling of Bulk Solids," to be submitted to *Spectrochim. Acta*.
2. D. L. Miller and A. Scheeline, "Pinch Coil Design and Pinch Plasma Dynamics," to be submitted to *Appl. Spectrosc.*

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

DATE
FILMED

6 / 7 / 93