Coolside Waste Management Research

(Project No. DE-AC21-MC91MC28162)

Quarterly Technical Progress Report

for the Period

April 1, 1992 to June 30, 1992

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Center for Applied Energy Research
University of Kentucky
3572 Iron Works Pike
Lexington Kentucky

July 23, 1992

MASTER

COOLSIDE WASTE MANAGEMENT RESEARCH

Technical Progress Report

Contract No: DE-AC21-91-MC8162

Report Period: June 1, 1992 to June 30, 1992

Statement of Project Objectives

Produce sufficient information on the physical and chemical nature of Coolside waste to design and construct physically stable and environmentally safe landfills.

Summary of Progress for Period

No additional swell on samples reported last month has been observed. The permeability of a specimen remolded near 100% of standard dry density and optimum moisture content and aged 14 days was 7.43×10^{-6} cm/sec. Unconfined compressive strength tests and unconsolidated undrained triaxial tests were also performed and are reported.

Work has been initiated toward filling the field lysimeters. Materials, equipment and supplies are being specified and ordered including 30,000 lbs of Ottawa sand to serve as the base layer in the lysimeters.

Subtask 2.2 - Chemical and Mineralogic Analysis of the Materials

Samples of the sand and the soils that will be used in filling the field lysimeter cells will be analyzed by the TCLP extraction technique to determine if any impurities are present that may complicate interpretation of the overall results. Of particular concern is the presence of adsorbed or occluded soluble species that may leach out during the early stages of the leaching thereby possibly generating significant impurities in the initial leachate samples. Since Ottawa sand will be used in the bottom of these cells samples have been obtained that will be run through the leaching procedure and the leachates analyzed for trace metal and anion composition.

Work on setting up the lab scale lysimeters is progressing. These units will be run in conjunction with the field work and provide a check on the field lysimeter behavior. In addition, pellets from Consul have been received and the TCLP on those samples are in progress. Results will be reported when completed.

Subtask 2.3 Geochemical Characterization of the Waste

Swell Testing - Monitoring of swell on Coolside solid waste samples compacted in CBR molds continued. No increase in swell has occurred since the last reporting period. Specimens were compacted near ninety five percent of standard maximum dry density and optimum water content in six in. diameter CBR molds (4.584 in. height). Swell is being monitored under the following conditions:

1. No aging time, 12.5 lb. surcharge weight
2. No aging time, 2.5 lb surcharge weight
3. 7 days aging, 12.5 lb. surcharge weight
4. 14 days aging, 2.5 lb.surcharge weight

Samples tested under conditions 3 and 4 were aged in a sealed plastic bags after they were compacted in the mold. Surcharge weight was placed on the sample after aging. The 2.5 lb. surcharge weight is the weight of the baseplate and stem used to measure swell. The 12.5 lb. surcharge weight is a typical weight used in CBR tests.

A second series of swell tests were performed in laboratory odometers. In these tests Coolside sample nos. 388, 397, 1040 and 1050 remolded near ninety five percent of standard maximum dry density and optimum moisture content, and aged for seven days at room temperature were placed into a 2.5 in. diameter by 1 in. mold. These samples showed small amounts of swell (less than .02 in.) until approximately 110 hours. After this time swell (less than .05 in.) has increased. Data obtained from swell tests are presented in Figures 1 through 4.

Figure 1. Swell versus time: 12.5 lb. surcharge, no aging time

Figure 2. Swell versus time: aged CBR samples.

Figure 3. Swell versus time: 2.5 lb. surcharge, no aging time.

Figure 4. Odometer swell: 7 days aging time.

Permeability - Results of two permeability tests were incorrectly reported last month. Coefficients of permeability for samples remolded near 100% of maximum standard density are 1.13×10^{-5} and 9.18×10^{-6} cm/sec for samples aged one and seven days, respectively, not 1.13×10^{-8} and 9.18×10^{-8} cm/sec as reported. A permeability test was performed on a specimen remolded near 100% of standard dry density and optimum moisture content, aged at room temperature for fourteen days. The coefficient of permeability was 7.43×10^{-6} cm/sec. Results of permeability tests performed on specimens remolded near 100% of maximum standard density are listed in Table 1.

Table 1. Results of permeability tests on specimens remolded near 100% of maximum standard dry density.

Sample ID Aging Time	Coefficient of permeability (cm/sec)	Dry Density (lbs./ft ³)	Moisture Content (%)	Moisture Content after Test (%)
1040-7 1 day	1.13×10^{-5}	70.32	35.72	47.55
1040-2 7 days	9.18×10^{-6}	71.18	36.92	46.76
1040-4 14 days	7.43×10^{-6}	70.83	37.78	47.96

Unconfined Compressive Strength - Unconfined compressive strength tests were performed on specimens remolded near 100% of standard dry density and optimum moisture content. These samples were aged at room temperature for fourteen and twenty eight days. Unconfined compressive strength for these tests was 112.9 and 528.9 psi, respectively. One test was performed on a specimen remolded near 95% of modified dry density, aged for twenty eight days. Results of unconfined compressive strength tests performed on samples remolded near 95% of low energy, standard, and modified maximum dry density are presented in Figure 5.

Figure 5. Unconfined compressive strength of specimens remolded near 95 % of low energy, standard, and modified dry density.

Triaxial Tests - Unconsolidated undrained (UU) triaxial tests were performed on Coolside solid waste specimens compacted near 95% of standard dry density and optimum moisture content. Tests were performed on samples which were aged for one and seven days. Results of U tests are presented in Table 2.

Table 2. Results of unconsolidated undrained triaxial tests.

Sample 1050 95% Standard	phi (degrees)	cohesion (psi)
1 day age time	28.2	1757.6
7 days age time	33.7	1253.7

Task 3 Leaching Studies

With NEPA approval to proceed with this program work at the field lysimeter site has been moving ahead. The plan is to bracket the Coolside waste in each of the cells between a lower layer of sand and a top layer of soil. The sand that will be used is Ottawa Crystal Sand and the final selection of soil has not as yet been made. The property of the soil is to allow percolation of rain water into the cells. Procurement of materials, equipment and supplies is progressing. Among the items to be procured are:

1. Thirty 44 x 44 inch pallets for drum transportation.
2. Steel banding (1/2 inch) for securing drums to pallets.
3. Rototiller for material mixing.
4. 750 and 325 gallon water tanks for transport to and on-side storage.
5. 10' x 10' frame and canvas for covering lysimeter.
6. Two 30 x 40 ft tarpaulins for on-site drum storage covers
7. 30,000 lbs of crystal Ottawa sand for 1 ft base pad in lysimeters.

These materials will be collected at Lexington and transported to the site when filling activities commence.

Work planned for next month

Subtask 2.2 - TCLP and complete trace metals analysis on crystal Ottawa sand will be completed. Benchscale leaching columns will be set up.

Subtask 2.3 - Permeability, unconfined compressive strength, and unconsolidated undrained triaxial testing will continue on remolded specimens.

Task 3 - Work will continue toward initiating the filling of the lysimeters located in Montgomery County, Kentucky. Coolside solid waste will be placed and compacted in the lysimeters. Density, moisture content and other geotechnical tests will be performed while the lysimeters are being filled.

COOLSIDE WASTE MANAGEMENT RESEARCH

Technical Progress Report

Contract No: DE-AC21-91-MC8162

Report Period: May 1, 1992 to May 31, 1992

Statement of Project Objectives

Produce sufficient information on the physical and chemical nature of Coolside waste to design and construct physically stable and environmentally safe landfills.

Summary of Progress for Period

The analytical protocol for the thick-target PIXE/PIGE analysis of the Coolside waste material has been completed. The PIXE analyses results of the NIST 1633a sample demonstrates the accuracy and relative precision of these measurements. The simultaneous PIGE analyses provide concentration information for Li, F, Na and Al using the NIST 1633a as the reference material. Additional PIGE data on Si, P and Mg in these samples will be forthcoming. The elemental concentrations determined by PIXE/PIGE in the pilot plant samples are compared with the Coolside Run 3 samples. The concentrations of Al and Fe in the pilot plant material is lower than the Coolside material while the Ca content of the pilot plant material is more than twice the Ca concentration found in the Coolside waste. The Na concentration of the pilot materials is consistent with the operating parameters of the pilot production tests; c.a. 2 wt. % in test 1 and 2 and 0.18 wt. % in test 3 and 4.

Swell tests were run on Coolside specimens compacted near ninety five percent of standard maximum dry density and optimum water content. Both fresh and 7 day aged samples with both 2.5 and 12.5 lb surcharge weights were evaluated. The swelling rates of the non-aged samples were greater than the rates of the aged samples. In another series of swell tests using laboratory odometers (2.5 in. diameter by 1 in. height) initial swelling occurred at a quicker rate than for the CBR samples. Coefficient of permeabilities for specimens remolded near 100% of standard dry density and optimum moisture content aged at room temperature for one and seven days were 1.13×10^{-8} and 9.18×10^{-8} , respectively. Permeabilities of specimens remolded near 90% of standard dry density and aged for 56 days continued to decline over earlier results. Unconfined compressive strength tests on samples remolded near 100% of standard dry density and optimum moisture content and aged at room temperature for one and seven days were essentially the same and did not follow previously established trends. These tests will be repeated.

Subtask 2.2 - Chemical and Mineralogic Analysis of the Materials

Coolside Waste Material - We have completed the development of the analytical protocol for the thick-target PIXE/PIGE analysis of the Coolside waste material. The fly ash is first oven dried for 24 hours at 105°C. Samples are then prepared by mixing 100 mg of the dried ash with 200 mg of high purity graphite (Johnson Matthey, Ultra F) in a methyl methacrylate mixer-mill vial and pressing c.a. 100 mg of this mixture into a pellet at 90 MPa in a 13-mm diam. stainless steel die. The samples are then irradiated for 10 min. with an external 2.5 MeV proton beam in 1 atm. of He. The PIXE analyses are standardized using a series of "elemental" samples prepared by spiking high purity graphite with single and multielement NIST SRM spectrometric solutions. Results of the PIXE analysis of three pellets prepared from the fly ash reference material NIST 1633a are given in Table 1 to demonstrate the accuracy and relative precision of the measurements. Note that while the simultaneous PIGE analysis also provides concentration information for the light elements Li, F, Na and Al, no values are given for these elements as these measurements are performed using the comparative method with NIST 1633a as the reference material.

The results of the PIXE/PIGE analysis of 97 Coolside waste samples from Run 3 (Barrels 305 through 401) are given in Table 2. The wide range of concentration values observed for most of the elements indicates that, as one would expect, the Coolside waste is a very heterogeneous material. For this reason, it is important to investigate the composition of a large number of samples in order to obtain a reasonable estimate of the elemental composition of the waste. The analysis of one sample from Run 3 by both XRF and ICP/DCP is also given. The discrepancy between the Pb values from the three techniques can be attributed to the inaccuracy in the PIXE results presented in Table 1. We are currently working to improve the accuracy of the measurements for Pb.

The concentration of the major elements determined by PIXE/PIGE in samples from Run 3 are plotted against Barrel number in Figure 1. It is clear that the calcium and titanium content of the Coolside waste varied with time during Run 3. It also appears that there was a change in the sodium content during the run. The average Na concentration of samples 305 to 347 is 1.26 ± 0.03 at the 99% confidence level while the average Na concentration of samples 348 to 401 is 1.18 ± 0.02 at the 99% confidence level. An effort will be made to correlate this variation with the operating parameters of the plant during Run 3.

Characterization of Pilot Plant Coolside Waste Samples - The concentration of the elements determined by PIXE/PIGE in the pilot plant samples are compared with the average values for the Coolside Run 3 samples in Table 3. It is clear from the concentrations of Al and Fe that the ash content of the pilot plant material is lower than the Coolside materials. On the other hand, the Ca content of the pilot plant material is more than twice the Ca concentration found in the Coolside waste. The Na concentration of the pilot materials is consistent with the operating parameters of the pilot production tests; c.a. 2 wt. % in test 1 and 2 and 0.18 wt. % in test 3 and 4. While the difference

Table 1. Instrumental PIXE analysis of NIST fly ash standard 1633a.^a

Element	PIXE (n=3)	RSD (%)	Certified Value	Obs/Actual
K	1.7 ± 0.1	5.9	1.88 ± 0.06	0.93
Ca	1.08 ± 0.04	3.5	1.11 ± 0.01	0.98
Ti	0.78 ± 0.02	3.3	[0.82 ± 0.04] ^b	0.97
V	279 ± 19	6.8	297 ± 6	0.94
Cr	186 ± 7	3.6	196 ± 6	0.95
Mn	166 ± 9	5.3	179 ± 8	0.93
Fe	9.1 ± 0.3	3.1	9.4 ± 0.1	0.97
Ni	135 ± 16	12	127 ± 4	1.06
Cu	118 ± 6	5.2	118 ± 3	1.00
Zn	216 ± 7	3.4	220 ± 10	0.98
Ga	60 ± 3	5.8	[56 ± 3] ^b	1.03
Ge	30 ± 6	18	[33.9 ± 0.2] ^b	0.88
As	141 ± 4	3.0	145 ± 15	0.98
Se	12 ± 2	18	10.3 ± 0.6	1.17
Rb	139 ± 8	5.9	131 ± 2	1.06
Sr	780 ± 30	4.0	830 ± 30	0.95
Y	74 ± 9	12	[82 ± 6] ^b	0.90
Zr	231 ± 15	6.4	[330 ± 80] ^b	0.70
Nb	24 ± 4	15	[28] ^b	0.86
Mo	26 ± 9	35	[29] ^b	0.90
Ba	1260 ± 100	7.9	[1500] ^b	0.84
Pb	94 ± 30	28	72.4 ± 0.4	1.44

a. Concentration in weight percent

b. Non-certified, compilation value¹

¹ E.S. Gladney *et al.*, Standard Reference Materials Compilation of Elemental Concentration, Data for NBS Clinical, Biological, Geological and Environmental Standard Reference Materials, NBS Spec. Publ. 260-111 (1987).

Table 2. Elemental composition of 97 Coolside waste samples by PIXE/PIGE analysis and one Run 3 sample by XRF and ICP/DCP.

Element	Coolside Barrels 305-401 (n=97)			n=1 XRF	n=1 ICP/DCP
	Avg.	Max	Min		
Al (%)	9.5 ± 0.8	13.2	7.7		9.68
Ca (%)	8.2 ± 1.4	11.3	5.6	10.61	10.0
Fe (%)	5.9 ± 0.5	7.3	4.9	7.98	7.10
K (%)	1.14 ± 0.07	1.3	1.0	1.43	1.66
Na (%)	1.22 ± 0.08	1.42	1.00	1.16	1.25
As	227 ± 16	277	191		
Ba	270 ± 95	570	74	383	334
Br	124 ± 11	150	96		
Cu	82 ± 8	98	63	92	70
F	415 ± 60	654	286		
Ga	39 ± 5	50	29		
Ge	49 ± 4	61	3		
Li	81 ± 12	129	59		
Mn	100 ± 11	129	76	138	132
Mo	29 ± 7	46	10	47	33
Ni	78 ± 11	167	61	191	159
Pb	74 ± 11	104	46		27
Rb	101 ± 10	127	80		
Sc	197 ± 49	340	57		
Se	15 ± 4	24	6		
Sr	322 ± 33	386	121		
Ti	3291 ± 220	3825	2881		4500
V	172 ± 11	197	143	149	
Y	61 ± 8	75	42		
Zn	292 ± 25	424	241	322	216
Zr	153 ± 18	239	110		

Figure 1. Metal Distribution in Drum Samples

Table 3. Elemental Composition Of Pilot Plant and Coolside Wastes by Instrumental PIXE/PIGE Analysis.

Element	Test 1	Test 2	Test 3	Test 4	Barrels 305-401		
					Avg.	Max	Min
Al (%)	5.5 (0.3)	6.3 (1.4)	5.4 (0.4)	4.7 (0.4)	9.5 (0.8)	13.2	7.7
Ca (%)	24.1 (0.7)	17.2 (0.5)	21.1 (0.2)	27.0 (0.1)	8.2 (1.4)	11.3	5.6
Fe (%)	3.72 (0.05)	4.48 (0.02)	4.22 (0.02)	3.34 (0.01)	5.9 (0.5)	7.3	4.9
K (%)	0.78 (0.08)	0.72 (0.02)	0.80 (0.03)	0.78 (0.02)	1.14 (0.07)	1.3	1.0
Na (%)	2.08 (0.03)	2.03 (0.04)	0.18 (0.01)	0.18 (0.01)	1.22 (0.08)	1.42	1.00
As	43 (9)	54 (4)	50 (5)	36 (4)	227 (16)	277	191
Br	10 (2)	12 (1)	0 (0)	1 (2)	124 (11)	150	96
Cu	31 (8)	35 (7)	27 (4)	21 (3)	82 (8)	98	63
Ga	18 (1)	22 (5)	21 (1)	12 (2)	39 (5)	50	29
Ge	13 (1)	20 (2)	14 (1)	10 (1)	49 (4)	61	36
Mn	78 (0)	88 (9)	80 (1)	69 (1)	100 (11)	129	76
Mo	14 (1)	0 (0)	14 (1)	11 (4)	29 (7)	46	10
Ni	39 (3)	25 (3)	24 (0)	32 (1)	78 (11)	167	61
Pb	11 (1)	8 (2)	14 (2)	18 (1)	74 (11)	104	46
Rb	39 (3)	51 (4)	41 (7)	39 (0)	101 (10)	127	80
Sc	868 (85)	635 (23)	685 (128)	728 (57)	197 (49)	340	57
Se					15 (4)	24	6
Sr	389 (3)	461 (4)	417 (25)	399 (1)	322 (33)	386	121
Ti	1214 (94)	1602 (32)	1501 (63)	1087 (29)	3291 (220)	3825	2881
V	150 (2)	157 (1)	163 (3)	149 (2)	172 (11)	197	143
Y	11 (4)	14 (4)	18 (1)	15 (8)	61 (8)	75	42
Zn	60 (1)	73 (1)	76 (2)	54 (3)	292 (25)	424	241
Zr	91 (9)	99 (12)	95 (5)	63 (5)	153 (18)	239	110

() Standard deviation.

in the concentration of most of the trace elements can be attributed to the lower ash content of the pilot samples, it is interesting to note that the Sc concentration of the Coolside samples is considerably lower than the values observed in the pilot materials and the Sr concentration of the Coolside and pilot samples is nearly equal. The Sr values can be attributed to the higher Ca content of the pilot materials; one would expect enhanced Sr with higher Ca. Although we have no explanation for the high Sc values in the pilot materials at this time, an analysis of the limestone used in the pilot plant runs may account for the high Sc values.

Subtask 2.3 Geochemical Characterization of the Waste

Swell Testing - Swell tests were initiated on Coolside solid waste. Specimens were compacted near ninety five percent of standard maximum dry density and optimum water content in six in. diameter CBR molds (4.584 in. height) in one series of tests. Swell is being monitored under the following conditions:

1. No aging time, 12.5 lb. surcharge weight
2. No aging time, 2.5 lb surcharge weight
3. 7 days aging, 12.5 lb. surcharge weight
4. 14 days aging, 2.5 lb.surcharge weight

Samples tested under conditions 3 and 4 were aged in a sealed plastic bags after they were compacted in the mold. Surcharge weight was place on the sample after aging. The 2.5 lb surcharge weight is the weight of the baseplate and stem used to measure swell. The 12.5 lb. surcharge weight is a typical weight used in CBR tests.

Another series of swell tests were performed in laboratory oedometers. In these tests Coolside sample nos. 388, 397, 1040 and 1050 were remolded near ninety five percent of standard maximum dry density and optimum moisture content into a 2.5 in. diameter by 1 in. height sample. Initial swell occurred at a quicker rate than the CBR samples. Data obtained from swell tests are in Figures 2 through 5.

Permeability - Permeability tests were performed on specimens remolded near 100% of standard dry density and optimum moisture content. These samples were aged at room temperature for one and seven days. Coefficient of permeabilities for these samples were 1.13×10^{-8} and 9.18×10^{-8} , respectively. A permeability test was performed on a specimen remolded near 90% of standard dry density, aged for fifty six days. Results of permeability tests performed on samples remolded near 90% of standard maximum dry density are presented in Figure 6. No permeability tests were performed in May on samples remolded near 95% of maximum standard, low energy, or modified dry density. Samples remolded near 100 % of standard dry density will be shown graphically when more data is available.

Figure 2.. Swell versus time: 12.5 lb. surcharge, no aging time.

Figure 3 Swell versus time: aged samples.

Figure 4. Swell versus time: 2.5 lb. surcharge, no aging time.

Figure 5. Odometer swell: no aging time.

Figure 6. Permeability of specimens remolded near 90% of standard dry density.

Unconfined Compressive Strength

Unconfined compressive strength tests were performed on specimens remolded near 100% of standard dry density and optimum moisture content. These samples were aged at room temperature for one and seven days. Unconfined compressive strength for these tests was 41.94 and 40.90 psi, respectively. These values are not following trends previously established trends where unconfined compressive strength increases with curing time. These tests will be repeated to determine if an error occurred while recording test data. One test was performed on a specimen remolded near 90% of modified dry density, aged for ninety days. Results of unconfined compressive strength tests performed on samples remolded near 95% of low energy, standard, and modified maximum dry density are presented in Figure 7.

Task 3 Leaching Studies

The eight cells of the lysimeters have been cleaned and temporary covers have been put in place. The mixing pad (8 ft x 15 ft) was completed and the site has been prepared for loading activities. One of the 4 additional available cells will be used for water storage which will be trucked from Mount Sterling. Samples of the water are being checked for trace metal concentrations.

Figure 7. Unconfined compressive strength of samples remolded near 95% of low energy, standard, and modified dry density.

Unconfined Compressive Strength

Unconfined compressive strength tests were performed on specimens remolded near 100% of standard dry density and optimum moisture content. These samples were aged at room temperature for one and seven days. Unconfined compressive strength for these tests was 41.94 and 40.90 psi, respectively. These values are not following trends previously established trends where unconfined compressive strength increases with curing time. These tests will be repeated to determine if an error occurred while recording test data. One test was performed on a specimen remolded near 90% of modified dry density, aged for ninety days. Results of unconfined compressive strength tests performed on samples remolded near 95% of low energy, standard, and modified maximum dry density are presented in Figure 7.

Task 3 Leaching Studies

The four cells of the lysimeters have been cleaned and temporary covers have been put in place. The mixing pad (8 ft x 15 ft) was completed and the site has been prepared for loading activities. One of the cells will be used for water storage for moistening samples. The water, which will be trucked from Mount Sterling, will be checked for trace metal concentrations.

COOLSIDE WASTE MANAGEMENT RESEARCH

Technical Progress Report

Contract No: DE-AC21-91-MC8162

Report Period: April 1, 1992 to April 30, 1992

Statement of Project Objectives

Produce sufficient information on the physical and chemical nature of Coolside waste to design and construct physically stable and environmentally safe landfills.

Summary of Progress for Period

Data have been developed from both batch and lab-scale column leaching studies on the Coolside waste. The TCLP, EPTOX and two tentative ASTM procedures were used. In the batch extraction tests the concentrations of the 8 RCRA metals were all below the trigger levels as set forth in CFR 40, with the majority below the instrument's detection limits. The ASTM extracts produced higher concentrations of the major and some trace metals because of the higher solids to liquid ratio in the extraction procedure. Potassium, sodium and selenium all show this pattern. Preliminary column leaching studies were performed, one on a loosely packed column and the second on a tightly compacted column. Very little difference was observed in the migration rate of water through the columns and channeling was not apparent. Overall, the Coolside waste material exhibits none of the hazardous waste characteristics of a RCRA non-exempt material. However, since the leachate exhibits a high pH, the leachate from the field lysimeter will have to be treated prior to disposal.

Under the Unified and AASHTO index testing and classification systems all Coolside samples evaluated thus far were classified as CL and A-4 (0), respectively. Permeability tests have been performed on 1 to 67 day aged samples remolded near 95% of maximum low energy, standard, and modified dry density. Samples remolded to low energy density were approximately 4% below optimum moisture content while the others were compacted at near optimum moisture content. Permeability coefficients ranged from 0.05 to 8.46×10^{-5} cm/sec. Unconfined compressive strength tests were performed on specimens remolded near the same densities and moisture contents as the permeability samples. They showed strength increased from 17.9 psi after 1 day aging to 1044.6 psi after 93 days aging. Additional unconfined strength tests on samples remolded to 90% of standard maximum dry density ranged from 22.9 psi after 1 day aging to 344.9 psi after 28 days.

Subtask 2.2 - Chemical and Mineralogic Analysis of the Materials

Both batch and lab-scale column leaching studies were conducted to assess the behavior of the Coolside material in the field lysimeter studies. Results from the TCLP, which is the standard EPA procedure for evaluating the heavy metal leaching properties of waste materials, was compared with the EPTOX and two other tentative ASTM procedures. In addition to batch extractions, two columns were also investigated. One was loosely packed with the Coolside material while column two was tightly compacted. The leachate from both columns were collected over a six week period and analyzed.

Extraction Procedures - Four extractions were performed on the Coolside material. Two proposed ASTM procedures, i.e., ASTM A and B, and two standard EPA extractions, i.e., EPTOX and TCLP were used. The two ASTM procedures operate at a solid to liquid ratio of 1:4, which is more concentrated than both EPA procedures which operate at a 1:20 ratio. ASTM A used distilled water while ASTM B used a sodium acetate-acetic acid buffer, which is comparable to the sodium acetate buffered extraction fluid used in the TCLP (Extraction fluid #1). All extractions were performed under controlled conditions as dictated by the various procedures. After addition of the extraction medium to the solid samples they were placed on a Lab-Line Orbit Environ-Shaker that provided constant movement of the aqueous phase operating at 70 one-inch strokes per minute without the incorporation of air. (See Extraction Procedures Table) The two ASTM methods are described as being a rapid method for obtaining a solution for evaluation of the extractable materials from a waste in order to provide an estimate of the relative environmental hazard associated with a particular waste sample.

Characteristics	Extraction Procedures			
	TCLP	EPTOX	ASTM-A	ASTM-B
Leaching Media	pH 2.88 buffer	Dist. H ₂ O (pH 4.8-5.2)	Dist. H ₂ O	pH 4.5 buffer
Solid:Liquid Ratio	1:20	1:20	1:4	1:4
Test Duration	18 hrs	24 hrs	48 hrs	48 hrs
Particle Size	<1 cm	<1 cm	(As Disposed)	

The EPTOX extraction is the procedure formerly used by the EPA in the determining the toxic characteristic of a waste. The EPTOX uses a 0.5 N acetic acid solution to buffer the sample to a pH of 5 after diluting with water. The amount of acid used can be no more than 4 times the sample weight with the solid to liquid ratio being 1:20. Agitation of the sample was implemented by placing the sample with DI water and buffer solution into a beaker with a stir bar, placed on a stir plate and mixed for 24 hours.

The TCLP like the EPTOX requires a 1:20 solid to liquid ratio and a buffer solution determined by the pH performed on the solid sample. The extraction medium (extraction fluid #2) was composed of acetic acid measured at a pH of 2.88. The amount of extraction fluid was determined as follows:

$$\text{wt of extraction fluid} = \frac{20 \times \% \text{ solids in sample} \times \text{wt of waste}}{100}$$

The sample was then placed into a Lars-Lande rotary extractor that rotates at 30 rpm for 18 hours. The sample was filtered through a pressure filter and the extract was then analyzed.

Analytical Procedures - The analytical data presented in this report were obtained by following the specific EPA Methods including: 1) SW-846, Test Methods for Evaluating Solid Waste; 2) EPA Method 1620, Metals by Inductively Coupled Plasma Atomic Emission Spectroscopy; and 3) Method 300.0, The Determination of Inorganic Anions in Water by Ion Chromatography. Conductivity and pH determinations were made using classical electrometric techniques. An Orion microprocessor ion analyzer/901 was used to measure pH while a YSI model 32 conductance meter measured conductivity.

Major and trace metals were analyzed by using a Spectrametrics DCP-AES and a Spectrametrics ICP-AES in conjunction with a CETAC U-5000 Ultrasonic Nebulizer. As, Se, and Hg were analyzed by the classic hydride method using a Perkin-Elmer FIAS (Flow Injection Analysis System) along with the Perkin-Elmer 3100 Atomic Absorption unit. Data presented in the tables are expressed as mg/l (ppm) unless otherwise noted.

Leachate Analysis and Comparison - The leachate data in Table 1 contain the results from the four extraction procedures. As mentioned the primary objective of the study was to determine the potential toxicity of the Coolside material using the TCLP and comparing the other extractions to this procedure. Ultimately the Coolside material passed the limits set forth by RCRA (Resource Conservation and Recovery Act) in this toxicity characteristic procedure. The eight EPA metals were all well below the limits.

There were no major surprises resulting from these extraction procedures. The concentrations of the majority of the trace metals were below the instrument's detection limits. A general comparison reveals a pattern showing the ASTM extracts producing higher concentrations of the major and some trace metals. The higher concentrations point to the solid to liquid ratios of the ASTM procedures as compared to the EPA extracts, (Ratios 1:4 as opposed to 1:20, accordingly.) ASTM-B extract shows a higher concentration than the ASTM-A extract, most likely due to the buffer added to ASTM-B. The TCLP also shows higher yields than the EPTOX because of the lower pH buffer and a more rigorous agitation method. K and Se show this pattern easily observed from Figures 1 and 2. There are, however, some anomalies in the data base such as Mg in which the concentration is much higher in the TCLP than in the ASTM extracts as shown in Figure 3.

Figure 1
K

Figure 2
Se

Column Leachate - A preliminary column leachate study was performed on the Coolside material in order to predict the leaching characteristics that will occur in the field and the lab. Secondly, the columns were prepared to study the migration of water through the column and observe the swelling capacity of the material. Two columns were assembled. Column one was loosely packed while column two was tightly compacted with the use a wooded dowel and human mechanics. Very little difference was observed in the migration rate of water through the columns and channeling was not apparent. Data on the loosely packed column which was taken over a 44 day period are shown in Table 2. The corresponding data on the compacted column taken over the same period are shown in Table 3.

Table 1. Waste Extraction Method Leachate Test Results

Element	TCLP	EPTOX	ASTM-A	ASTM-B
Al	<.05	<.05	<.05	<.05
Ag	<.01	<.01	<.01	<.01
As	.014	<.0005	.013	.017
Ba	.235	1.08	.35	.37
Be	<.0001	<.0001	<.0001	<.0001
Ca	.27 %	.14 %	.12 %	.20 %
Cd	<.001	<.001	<.001	<.001
Co	<.005	<.005	<.005	<.005
Cr	.004	.008	.020	.019
Cu	<.003	<.003	<.003	<.003
Fe	.192	<.005	<.005	<.005
Hg	<.0005	<.0005	<.0005	<.0005
K	36.0	26.0	110.0	120.0
Mg	.270	.023	.021 [*]	.065
Mo	.353	<.005	<.005	<.005
Na	685.0	514.0	.11 %	.12 %
Ni	<.005	<.005	<.005	<.005
P	<.005	<.005	<.005	<.005
Pb	<.02	<.02	<.02	<.02
Se	.204	.138	.434	.460
Si	.710	.070	.490	.550
Ti	.010	<.002	<.002	<.002
V	.003	<.003	<.003	<.003
Zn	.005	.005	.006	.004

Table 2. Loose-Packed Column Leachate Data

Date/ days	Inches Added	pH	Cond.	Ca	K	Na	Cl	SO4
7	6	12.45	58.80	1770	715	14800	15107	7857
8	7	12.42	52.81	1280	745	15500	16769	8083
9	8	12.38	39.90	870	480	9300	10791	5965
12	9	12.55	29.90	870	444	7700	6801	4674
13	10	12.41	29.40	850	372	5250	5446	4395
14	11	12.56	24.60	820	378	5000	4636	4194
15	12	12.81	23.80	812	380	4750	3771	4132
16	13	12.81	23.60	761	370	4300	2862	4234
19	14	12.88	22.50	564	387	4100	1897	4153
20	15	12.86	20.50	600	407	3550	1907	4181
21	16	12.86	17.40	620	365	2800	674	3032
22	17	12.86	14.60	615	285	1850	382	2157
23	18	12.83	11.90	682	260	1230	200	1165
26	19	12.71	10.70	374	360	865	121	337
27	20	12.74	10.00	459	404	620	91	118
28	21	12.60	10.20	484	433	438	81	47
29	22	12.61	9.80	487	480	393	72	22
30	23	12.71	9.30	470	496	335	74	16
33	24	12.62	9.10	402	540	310	56	7
34	25	12.70	8.30	441	575	264	50	5
35	26	12.72	8.10	483	552	232	43	5
36	27	12.73	8.20	514	522	206	34	4
37	28	12.68	7.80	504	490	177	30	4
40	29	12.65	7.90	492	510	167	30	4
41	30	12.59	7.90	448	510	177	28	3
42	31	12.55	7.80	420	490	152	25	3
43	32	12.59	7.40	410	485	111	24	3
44	33	12.59	7.30	500	400	100	24	3

Table 3. Compacted Column Leachate Data

Date/ Days	Inches Added	pH	Cond.	Ca	K	Na	Cl	SO4
8	7	12.40	63.6	1250	955	18550	24396	11552
9	8	12.30	65.4	887	972	18700	23778	10872
12	9	12.46	61.0	897	1050	18800	19591	9613
13	10	12.33	56.8	846	902	11200	18266	9871
14	11	12.54	39.8	770	680	9000	9243	8257
15	12	12.88	29.8	675	485	6400	4001	7047
16	13	12.85	26.4	635	362	4900	1718	6498
19	14	12.92	23.1	501	394	4400	788	5577
20	15	12.91	20.8	544	388	3800	455	4672
21	16	12.88	16.7	540	335	2800	253	3141
22	17	12.89	13.7	535	275	1620	150	1969
23	18	12.72	11.2	630	276	999	101	964
26	19	12.70	10.1	300	377	709	80	206
27	20	12.73	9.9	440	450	500	75	96
28	21	12.58	10.2	470	488	420	71	38
29	22	12.62	10.0	460	540	390	68	16
30	23	12.60	9.8	420	550	330	65	9
33	24	12.63	10.1	387	660	350	63	6
34	25	12.75	9.1	390	690	328	65	5
35	26	12.77	9.1	397	682	295	55	5
36	27	12.74	8.9	389	670	263	54	4
37	28	12.70	8.6	416	628	231	46	4
40	29	12.70	8.8	391	623	218	43	4
41	30	12.63	8.7	407	630	207	39	4
42	31	12.60	8.5	310	620	110	35	4
43	32	12.59	8.4	209	580	75	32	3
44	33	12.56	8.2	210	580	71	29	3

The pH of the column leachates indicate the Coolside waste is strongly alkaline with leachate pH values of 12.5 suggesting that the leachate from the field lysimeter will require treating before disposal. The major constituents of the leachates were SO₄, Cl, Na, and Ca. These cations and anions leached rapidly but reached equilibrium in a fairly short time. From Figure 4 it is apparent that these cations and anions level out within approximately 4 weeks.

Hazardous Waste Characteristics - Under RCRA there are four characteristics that are used to define non-exempted waste materials that designated hazardous waste. The definitions of these characteristics covered under that legislation are defined in the Code of Federal Regulations Volume 40.

1) Toxicity Characteristics: Waste materials which produce leachates in the TCLP having heavy metal concentrations equal to or in excess of the following limits are designated RCRA wastes.

Element	Limit (mg/l)	Coolside
Ag	5.0	<0.01
As	5.0	0.014
Ba	100.0	0.235
Cd	1.0	<0.001
Cr	5.0	0.004
Hg	0.2	<0.0005
Pb	5.0	<0.02
Se	1.0	0.204

2) Ignitability: A material is a RCRA waste if it exhibits a flash point of less than 140°F (60°C).

3) Reactivity: A material is a RCRA waste if it is unstable, reacts violently with water, is sufficiently cyanide or sulfide bearing to produce toxic gas, or is capable of detonation.

4) Corrosivity: A material is a RCRA waste if it exhibits a pH of less than 2.0 or greater than 12.5, or corrodes steel at a rate greater than 6.35 mm per year at 55 C.

The heavy metal concentrations in the Coolside material were less than those specified under TCLP. The material is a nonreactive inorganic solid and is completely non-combustible such that the Ignitability and Reactivity characteristic does not apply. The material exhibits a pH greater than 12.5 and would therefore be corrosive. However, since it is a solid material the Corrosivity characteristic does not apply. EPA's SW-846 Corrosivity test states that "A solid waste exhibits the characteristic of corrosivity if a representative sample is aqueous and corrodes steel". Since the Coolside material is non-aqueous this characteristic does not apply. However, for disposal purposes, the leachate from the field lysimeter will be considered corrosive. To supplement the corrosivity characteristic please see pH table below.

**pH Table -
Method 9045 (SW-846)***

Soil pH	Calcareous Soil pH
13.55	12.67

- * Method 9045 is an electrometric procedure which has been approved for measuring pH in calcareous and non-calcareous soils.

Non-calcareous soil: 20 grams of sample was placed in a 100 ml beaker along with 20 ml of DI water. The sample was stirred for 30 minutes then allowed to settle for 1 hour. The pH of the aqueous portion was then measured.

Calcareous soil: 10 grams of sample was placed in a 100 ml beaker along with 20 ml of a .01 M calcium chloride solution. The sample was stirred for 30 minutes then allowed to settle for 1 hour. The pH of the aqueous portion was then measured.

Subtask 2.3 Index Testing and Structural Properties Testing.

Index testing and classification by the Unified and AASHTO systems has been completed. Tests were performed on six samples identified as: sample 1, sample 3, and barrel nos. 388, 397, 1040, and 1050. All samples classified as CL and A-4 (0) by the Unified and AASHTO Systems, respectively, were non-plastic, and had 95% passing, the no. 200 sieve.

Four types of moisture-density relations tests were performed on the six samples: static - 17 psi (KTC method), low energy (KTC method), standard (ASTM D698), and modified (ASTM D1557). Table 4 summarizes results of moisture-density tests.

Table 4.

Sample ID	Static (17 psi)		Low Energy		Standard		Modified	
	Max. DD (lb/ft ³)	Opt. MC (%)	Max. DD (lb/ft ³)	Opt. MC (%)	Max. DD (lb/ft ³)	Opt. MC (%)	Max. DD (lb/ft ³)	Opt. MC (%)
1	48.7	40.4	65.8	45.3	69.5	35.5	79.1	27.6
3	48.7	40.0	65.1	44.6	69.9	36.5	77.1	29.3
388					70.8	39.4	76.8	29.1
397			64.0	47.0				
1040					71.1	35.8	76.6	29.4
1050			67.4	43.0				

Permeability

Permeability tests have been performed on samples remolded near 95% of maximum low energy, standard, and modified dry density. Specimens were remolded near optimum moisture content, except those compacted at 95% of low energy density. These samples were remolded approximately 4% below optimum moisture content. Samples tested have been aged at room temperature from 1 to 67 days. Coefficient of permeabilities have ranged from $.05 \times 10^{-5}$ to 8.46×10^{-5} cm/sec. Results of permeability tests performed to date are presented in Figure 5.

Figure 5. Results of permeability tests on specimens remolded near 95% of maximum low energy, standard, and modified dry density.

Unconfined Compressive Strength

Unconfined compressive strength testing is continuing on specimens aged from 1 to 93 days. The samples were remolded near the same densities and moisture contents as the permeability samples. Strength has increased from 17.9 psi (1 day aging) to 1044.6 psi (93 days aging,). Unconfined strength tests have been performed on samples remolded to 90% of standard maximum dry density. Strength has ranged from 22.9 psi (1 day aging time) to 344.9 psi (28 days). Results of unconfined compressive strength tests are located in Figures 6 and 7.

Unconfined compressive strength testing continued on some samples after permeability testing. These tests were performed when the specimen is in a saturated condition. Saturating the samples after aging is not affecting unconfined strength significantly. Strength is still increasing with aging time. Figure 8 compares unconfined strength of specimens aged at room temperature with those tested after a permeability was performed. Both sets of data represent samples remolded near 95% of standard maximum dry density.

Figure 6. Unconfined Compressive Strength vs. aging (95% standard dry density)

Figure 7. Unconfined Compressive Strength vs. aging (90% standard dry density)

Figure 8. Unconfined compressive strength of specimens remolded near 95% of standard maximum dry density, and unconfined strength after permeability testing.

Work planned for next month

Long term swell tests will be initiated. Two types of swell tests will be performed. In the first series samples will be prepared near 95% of standard dry density in a CBR mold (6" diameter, 4.58" height). Some samples will have a surcharge weight, others will not. The samples will be soaked, and swell monitored, for an extended period (100 days or more). Swell will be monitored in another series of tests by saturating remolded samples (2.5" diameter, 1" height) in an odometer. No surcharge will be on the samples. The smaller sample should saturate quickly; therefore, any swell should occur quicker than the samples in the CBR molds.

Permeability and unconfined compressive strength testing will continue on remolded specimens. Unconsolidated undrained triaxial shear tests will be performed.

Work will begin on loading the filed lysimeters, located in Montgomery County, Kentucky *if NEPA clearance is granted and permission is obtained from METC*. Coolside solid waste will be placed and compacted in the lysimeters. Density, moisture content and other geotechnical tests will be performed while the lysimeters are being filled.

END

**DATE
FILMED**

3 / 17 / 93