DEVELOPMENT OF AN INERT CERAMIC ANODE TO REDUCE ENERGY CONSUMPTION IN MAGNESIUM PRODUCTION

TECHNICAL PROGRESS REPORT TO
U. S. DEPARTMENT OF ENERGY
FOR WORK PERFORMED UNDER
COOPERATIVE AGREEMENT NO. DE-FC07-91ID13133

REPORTING PERIOD: 1/1/92 through 12/31/92

PREPARED BY

**ADVANCED CERAMICS LABORATORY &
CATALYSIS LABORATORY
CENTRAL RESEARCH & DEVELOPMENT
THE DOW CHEMICAL COMPANY
MIDLAND, MI 48674**

MASTER

DEVELOPMENT OF A CERAMIC ANODE TO REDUCE ENERGY CONSUMPTION IN MAGNESIUM PRODUCTION

1. INTRODUCTION

Magnesium metal is an industrially significant commodity. Consumption in the United States was 135,000 metric tons in 1989 according to the Bureau of Mines. Magnesium is produced primarily by the electrolysis of molten magnesium chloride in a process which also makes by-product chlorine. Based on the Gibbs energy of formation a minimum of 5.5 kwh/kg of power is required. However, estimates of the total cell electrical energy requirement range from 11 to 22 kwh/kg. Much of the excess energy consumed in production of magnesium comes from ohmic heating losses in the molten salt bath, the electrical busswork and the electrodes. Graphite anodes are consumed during electrolysis, increasing the distance between the electrodes. This accounts for an appreciable fraction of the ohmic losses. In addition, the consumption of graphite is a significant and quantifiable indirect energy loss.

The purpose of this work is to develop an inert, i.e. dimensionally stable, anode for the production of magnesium in electrolytic reduction cells currently used by The Dow Chemical Company. The approach is to start at laboratory scale and use a ceramic semiconductor material as the stable part of the anode. It will interface with the cell's bath and atmosphere. To compensate for the ceramic's higher resistivity compared to graphite, the ceramic is to be prepared as a thin hollow shell (tube) closed at one end. The ceramic shell is then to be filled with a high conductivity, both electrical and thermal, core. The core is to contain a metal component that provides the high conductivity. To compensate for the high thermal expansion of the metal, the core will contain ceramic particles in sufficient quantity to minimize the thermally induced stresses between the shell and core. Thus the anode is to be a ceramic tube filled with a metal-ceramic composite core. In contrast, Johnson and Miller (1) investigated a metal-clad (coated) titania plus 1 mole % Ta ceramic electrode directed toward use in a sodium-sulfur battery. The metal functioned as a current carrier only and was restricted to a thickness of ≤ 0.13 mm.

Past work here (2) has shown that titanium dioxide doped with tantalum pentoxide functions as a corrosion resistant material with electrical semiconductivity under cell conditions. However, cracking problems in fabricating and using (thermal shock failures) such ceramic tubes led to the work being discontinued. It is believed that the application of contemporary ceramic science and engineering methodologies can overcome those difficulties in an anode system designed as above.

2. RAW MATERIALS

The criteria for selecting the raw materials for fabricating the ceramic shell were as follows:

- ◊ Available in commercial quantities.
- ◊ High in purity ($\geq 99.5\%$).
- ◊ Suitable for use in the process of slip casting of greenware in gypsum plaster molds.

The major use for titania is as a pigment in products such as paints and plastics. These pigments often have additives. For example, most of the titania products sold by one large domestic chemical company contain alumina and silica as additives to make them more readily dispersible but also making them unsuitable for this use.

The material selected as the TiO_2 is from TAM CERAMICS, INC. and is called their TICON™ grade HP 59030. In Appendix A, Table A1 is a copy of the supplier's typical characteristics of that titania as well as a less pure grade.

The material selected as the Ta_2O_5 is from HERMANN C. STARCK BERLIN, GmbH & Co. KG, and is their "standard optical grade." Table AII in Appendix A is the analysis from the supplier for one lot of Ta_2O_5 purchased. Another supplier offers material of similar purity but was only available with a coarser particle size.

Both of the materials selected meet the first two criteria listed above. In the next section are described the procedures used to make them meet the third one.

3. GREENWARE FORMING-PROCESS DEVELOPMENT

The most important physical characteristics of the two ceramic raw materials as received are listed in Table I. Particle size distribution was measured by light scattering. Surface area was determined using the BET technique. Helium pycnometry was utilized for particle density measurements.

The titania is within the "typical properties" as listed by the supplier for surface area but the particle size, based on the D_{50} , is somewhat higher than the top of the range 1-5 μm listed. Starck's tantalum pentoxide is supplied with a nominal particle size of 90% minus 325 mesh (44 μm) and is somewhat larger than that with a measured D_{90} of 50 μm . Its surface area is low as expected with the large particle size. Both materials are too large in particle size to make good casting slips without grinding to a $D_{90} \leq 2 \mu\text{m}$.

Table I. Characteristics of Particles in as Received Raw Materials.

	Tantalum pentoxide	Titania
Particle Size Distribution (μm)		
D_{90}	50.07	12.91
D_{50}	25.36	5.82
D_{10}	7.45	1.67
Density (He pycnometer) (g/cc)	8.66	4.21
BET surface area (m^2/g)	0.468	3.54

Through the study of dispersion, dispersants, pH adjustment, and attrition milling the following has been found to produce excellent casting slips:

Adjust pH with a combination of citric acid and ammonium hydroxide while adding powders to deionized water in an attrition mill, maintaining the pH between 7.0 and 8.5 while attrition milling is continued for at least 11 hours and up to more than 24 hours. Final pH is adjusted to 8.0 ± 0.2

Since an 11 hour milling time extends beyond normal working hours standard procedures were worked out for slip preparation and casting that required no attention outside normal hours. A specific batch formulation and processing instructions for making 5 mole % Ta_2O_5 slip cast greenware for laboratory scale anode shells is included as Appendix B for illustration purposes. Milling is carried out in a 1400 cc capacity polymer coated attritor with 5 mm diameter yttria stabilized zirconia grinding media.

Anode shell greenware was slip cast in a one piece mold made from U. S. Gypsum Co.'s #1 pottery plaster. The mold is held in a pivoting framework on a cart and is shown in Figure 1.

Figure 1. Slip Casting Mold For Ceramic Anode Shells

4. SINTERING STUDIES

Prior studies(3,4,5) of sintering titania have shown high sintered density ($\geq 97\%$ of theoretical density) being achieved between firing temperatures of 900°C and 1550°C . The lowest temperature was for nanocrystalline (very active) powder and the highest for powder produced from having first been calcined (dead burned) at 1550°C . Johnson and Miller (1) sintered for 3 hr at 1400°C in air.

Sintering shrinkage of titania and titania plus 1 to 5 mole percent tantalum pentoxide was studied using a dilatometer (Theta Industries 1600°C system) with alumina holder and sensor rod. Titania (11 hr attrition) sintered for two hours at 1200°C - 1250°C in air yielded $\geq 99\%$ dense ceramics. The higher temperature results in a more than doubling of the grain size.

Figure 2 is a plot of density vs temperature for titania heated at $5^{\circ}\text{C}/\text{min}$ to 1200°C and held at that temperature for two hours. By immersion in water (Archimedean method) the bulk density was determined to be 99.0% of theoretical density (TD).

Addition of the tantalum pentoxide to titania was found to increase the sintering temperature at all additions in the 1-5 mole % range. With 5 mole % Ta_2O_5 added and an attrition time of 12 hr a two hour sinter at 1400°C produced a density of 98.1% of theoretical. Increasing the attrition time to 25 hours increased the sintered density to 99.6% of TD. Figure 3 shows the densification curve for this latter material with a 2 hr hold at 1400°C . Heating and cooling rates were $5^{\circ}\text{C}/\text{min}$ in both cases. The greenware density for the latter was 63 % of TD.

(NOTE: Theoretical density of the different mole ratio sintered compositions have not been experimentally measured. Values used are based on literature values for TiO_2 [4.26g/cc] and Ta_2O_5 [8.2g/cc] and the volumetric ratios of these in the different starting compositions.)

Figure 3. Density vs Temp. for Dilatometer
Sinter Run "M5%Ta25hr-1400°C/2hr"

5. CHARACTERIZATION OF CERAMIC—PHYSICAL

Greenware disks were prepared by both dry pressing and slip casting of a 95:5 mole ratio $\text{TiO}_2\text{:Ta}_2\text{O}_5$ for use in making flexural test bars. The powder for dry pressing was prepared by grinding dried slip that was similar to that used for casting. The disks were sintered for two hours at 1480°C and 1500°C respectively. The disks were then sent out for machining into flexural strength test specimens (4.0mm x 3.0mm x 45 mm) suitable for "configuration B" as outlined in ASTM C 1161-90, "Standard Test Method for Flexural Strength of Advanced Ceramics at Ambient Temperature." Specimens from both disks were tested in the "four-point- $\frac{1}{4}$ point" configuration under all conditions. Specimens from the dry pressed disk were tested at room temperature, 400°, 600°, and 800°C. Fewer specimens were available from the slip cast disk so they were tested only at room temperature and 800°C.

Young's modulus, bulk modulus, shear modulus and Poisson's ratio were measured at ambient conditions with a sonic technique on each of the flexural strength specimens before breaking. The results of this testing and the flexural testing are in Table II. The flexural strength test results as a function of temperature are shown graphically in Figure 4.

The values are greater for the slip cast material in every category in Table II where a direct comparison is possible. The strength at 600°C of the dry pressed sample is not consistent with the rest of the results, being greater than all but the slip cast sample at room temperature. This is clearly shown in Figure 4 where it falls above the line drawn between the two points for the slip cast sample. Other than noting the large standard deviation for this set of test bars, no explanation can be given for this anomaly. The room temperature strengths compare well with reference (1) where average four-point bend was reported to be > 18,000 psi for 1 mole % Ta doped ceramics. Elsewhere modulus of rupture values for TiO_2 are reported in the 18,000-22,000 psi range (6).

Table II. Physical Property/Characteristic Values for Moduli and Flexural Strength of Sintered 95/5 Mole % Titania/Tantalum Pentoxide Greenware Prepared by Both Slip Casting and Dry Pressing.

PROPERTY/CHARACTERISTIC	SLIP CAST	DRY PRESSED
DENSITY (gm/cc)	4.58	4.53
% DENSE	96	95
YOUNG'S MODULUS (psi x 10 ⁻⁶)	36	32
BULK MODULUS (psi x 10 ⁻⁶)	25	22
SHEAR MODULUS (psi x 10 ⁻⁶)	14	13
FLEXURAL STRENGTH (Ksi) @ Temperature (°C)		
23	26.0	20.7
400		19.5
600		23.2
800	20.0	16.8

Figure 4. Flexural Strength vs Temperature for 95/5 Mole % Titania/Tantalum Pentoxide

6. CHARACTERIZATION OF CERAMIC—ELECTRICAL

Achieving low electrical resistivity is an important goal of this work. A substantial part of a finished anode's resistance will come from the ceramic shell. How low a resistivity could be reached was not precisely known. A value of 0.10 ohm-cm at 700°C was targeted as a goal (1). Resistivity was determined using a four-point contact method. Samples were tested in air in a tube furnace.

Specimens for resistivity measurement testing were prepared by slip casting and sintering solid rods which were 12.5-15.0 cm long after sintering. The material does behave as a semiconductor,

i.e. the resistivity decreases as temperature increases. This can be seen from resistivity measured in two thermal cycles run on the same specimen as listed in Table III and shown graphically in Figure 4. This sample had 5 mole percent tantalum and had been sintered for two hours at 1500°C. The data from the two runs are in excellent agreement. Other samples, ranging from 1 to 5 mole % in Ta₂O₅ additions and sintering at temperatures from 1350°C-1500°C, had resistivities that varied from 0.11 to 0.50 ohm-cm at about 700°C. It appears that the 0.10 ohm-cm goal at 700°C is about the minimum achievable and may not be reached with every ceramic sample made.

Table III. Electrical Resistivity Values as a Function of Temperature for 95/5 Mole % TiO₂/Ta₂O₅ Sintered Ceramic Rod.

	Temperature (°C)	Resistivity (Ohm-cm)
<u>Run #1</u>	18	28.900
	110	4.930
	203	1.190
	284	0.500
	378	0.270
	474	0.180
	584	0.130
	656	0.110
	762	0.089
<u>Run #2</u>	20	14.400
	99	5.230
	192	1.270
	275	0.560
	365	0.300
	455	0.190
	548	0.140
	647	0.110
	737	0.090

Figure 5. Resistivity vs Temperature for 95/5 Mole % Titania/Tantalum Pentoxide Sintered Rod.

7. LAB SCALE ANODE DESIGN-STRESS ANALYSIS MODELING

The proposed structure of the ceramic anode requires proper matching of the coefficients of thermal expansion of the composite core material and the inert ceramic shell. A coupled dynamic heat transfer - thermal stress analysis, modeling study is being used to provide design information on geometry and material composition for laboratory scale ceramic anodes. For performing the modeling calculations, the commercially available computer program, trade named ABAQUS, was used. ABAQUS is a robust finite element program capable of making dynamic heat transfer and thermal stress calculations for complex geometries. The program inputs are geometry, moduli, coefficients of thermal expansion, temperature dependent thermal conductivities and specific heats, and the thermal and physical boundary conditions. The plan called for making an initial set of calculations early in the research program using material properties found in our literature search for the proposed core composite components copper and silicon carbide. Table IV presents the material values for selected materials used in this initial set of simulations.

Table IV. Material parameters used in anode simulations.

Material Parameters	Titanium Dioxide (TiO ₂)		Copper (Cu)		Silicon Carbide (SiC)		40-60 Composite (SiC/Cu)		50-50 Composite (SiC/Cu)	
Density (kg/m ³)	4.157x10+3		8.933x10+3		3.22x10+3		6.6478x10+3		6.05x10+3	
Expansion (10 ⁻⁶ /°C)	8		19		4.02		10		8.4	
Y Modulus (GPa)	283		111		428		140		173	
Poisson's Ratio	0.28		0.33		0.19		0.274		0.26	
Emissivity	0.8		0.03		0.8		0.4		0.4	
J/kg-K	Temp °C	Cv	Temp °C	Cv	Temp °C	Cv	Temp °C	Cv	Temp °C	Cv
	25	710	-75	356	25	675	25	415	25	528
	125	805	125	397	125	860	725	780	525	394
	325	880	325	417	325	1050			725	409
	525	910	525	433	525	1135				
	725	930	725	451						
W/m-K	Temp °C	k	Temp °C	k	Temp °C	k	Temp °C	k	Temp °C	k
	25	8.4	0	400	25	125	25	290	25	262
	125	7.01	25	398	200	100	725	238	725	210
	325	5.02	225	388	400	78				
	525	3.94	325	383	1300	35				
	725	3.46	725	352						

The ceramic anode modeled is comprised of a titania shell with a current carrying SiC/Cu composite core. Thermal stress modeling results on the lab scale anode, shown in Figure 6 for a specific titania shell thickness, reveals that the optimal core composition that

results in the lowest thermal stresses in approximately a 50/50 volume ratio SiC/Cu composite composition.

Figure 6. Maximum tensile stress as a function of core composition in the lab scale ceramic anode

The results also show that at higher percentages of SiC in the core composite, the thermal expansion mismatch and the increased modulus, or stiffness, of the core material results in increased tensile stress levels concentrated at the core-shell interface. Core materials with SiC component percentages less than 50% also experience increased tensile stresses but concentrated in the shell's rounded bottom area due to thermal expansion mismatch. These results point to pursuing the 50/50 SiC/Cu core composite to minimize thermal tensile stresses.

Simulations have also been performed on the potentially more severe, transient stress evolution that occurs in actual operation of the magnesium cell as the anode is initially placed into the reactor. Results from this simulation have shown that the optimized 50/50 SiC/Cu composite core anode design should survive the predicted transient thermal stress levels. Thus the results of these calculations on the lab scale anodes indicate that they should have little problem surviving the thermal stresses during any phase of operation testing.

8. Metal-Ceramic Core Development

Initially the development work on the high electrical conductivity core that would match the ceramic shell in thermal expansion was directed at a mixture of copper metal and silicon carbide powder. Copper, with its very high conductivity, could be less than half the volume of the core and more than meet the conductivity need of the system. Silicon carbide would "average" down the high thermal expansion of the copper if the two materials could be made to bond to each other and expand and contract as though a single phase.

In one of the first experiments with mixtures of the two materials, a 400 grit particle size SiC and a -325 mesh 99.5% pure copper powder, it became obvious that melted copper does not wet silicon carbide or the ceramic shell material. Pellets of the two mixed powders, at equal volumes, could be sintered but did not become strong and in thermal expansion behaved almost like pure copper. This is shown in Figure 7 for a sintered equal volume mixture that had been cold isostatically pressed at 40 Ksi. The thermal expansion coefficient is about 50-100 percent greater than the $7-9 \times 10^{-6}/^{\circ}\text{C}$ found in the literature for titania.

The nonwetting of the ceramic by the copper seems to preclude good electrical contact between the core and shell. The nonwetting of the SiC is probably the reason the thermal expansion of the sintered mixture is close to that of copper alone. Compositional studies will have to be done to achieve wetting/bonding of metal to ceramic.

**Figure 7. Expansion vs Temperature for Cu/SiC, 50/50
Volume %, Sintered at 1010°C for 2 Hr.**

9. Production of Ceramic Tubes For Anodes

The ceramic composition chosen for use in the anodes is titania plus 5 mole % tantalum pentoxide. It has had the lowest resistivity compared to 1 and 3 mole % compositions. With slip prepared as in Appendix B and the mold as shown in Figure 1, as many greenware anode shells can be prepared as needed.

Two sintered tubes are shown in Figure 8. They were sintered at 1400°C for 2hr. The closed end is hemispherical. The open end of the tube is 4.6 mm larger in diameter than the closed end (29.2 mm vs 24.6 mm). The taper is to facilitate the greenware's release and removal from the mold. The length is 380 mm (15 in) so that a finished anode can be at least 305 mm (12 in) long. Wall thickness at the open end has been varied between 2.5 mm and 5 mm. A 380 mm long tube with a 3.8 mm wall thickness weighs 500 g.

10. SUMMARY

Raw material selection, development of slip casting as the greenware forming method, and sintering studies have been completed. The external size and shape of the ceramic portion of the anode has been set. Wall thickness is a controlled variable. It is controlled by slip characteristics and casting time. Sintered tubes have been made with wall thicknesses between 2.5 mm and 5.0 mm. Establishment of optimum thickness will be based on test results from anodes. Modeling studies have shown the conceptual design should survive the stresses applied. Results of strength testing of slip cast and sintered titania-tantalum pentoxide ceramics prepared here exceed the values used in the model.

Work on the core will be broadened to incorporate materials that have the potential to cause bonding of the core's metal component and the ceramic particulate filler and the ceramic shell. The choice of copper and silicon carbide alone will not suffice. This is expected to require additional compositional work.

Figure 8. Sintered Anode Shells Ready for Composite Core

11. References

1. O. W. Johnson and G. R. Miller, "A Metal -Clad Electronic Ceramic Container and Electrode System," *Am. Ceram. Soc. Bull.*, **56** [8] 706-11 (1977).
2. a. S. F. Spangenberg, A. L. Finley, and D. J. Searson, "Electrolytic Cell and Anode for Molten Salt Electrolysis," U.S. Pat. No. 4 370 216 (1983).
b. S. F. Spangenberg, A. L. Finley, and D. J. Searson, "Process and Anode for Molten Salt Electrolysis," U.S. Pat. No. 4 448 654 (1984).
3. H. Hahn, J. Logas, and R. S. Averbach, "Sintering Characteristics of Nanocrystalline TiO_2 ," *J. Mater. Res.*, **5** [3] 609-14 (1990).
4. H. Wohlfromm, P. Pena, J. S. Moya, and J. Requena, "Slip Casting of TiO_2 ," pp. 1.211-1.217, in Euro-Ceramics, Vol. 1, *Processing of Ceramics*. Edited by G. de With, R. A. Terpatra, and R. Melselaar. Elsevier Applied Science, New York, 1989.
5. L. I. Verba and E. V. Degtyareva, "Rheological and Technoligical Properties of Titanium Dioxide Slips and the Properties of the Castings," *Ogneupory*, 1978, [3], 28-33.
6. "Titanium Dioxide," *Materials Handbook, Ceramic Industry*, 1992 [1], 102-104.

APPENDIX A: RAW MATERIAL DATA SHEETS
Table AI. Supplier's Data Sheet for Titania Powders

TICON® TiO₂ TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>GRADE</u>	
	<u>HG 52519</u>	<u>HP 59030</u>
Phase	Rutile	Rutile
TiO ₂ , %	98.80	99.95
Surface Area, M ² /g	2.0-2.5	2-5
PSA, D ₅₀ Micron	3.4	1-5*
Bulk Density, Lb./ft. ³	110	43
LOI, %	0.12	<0.2

* 0.1 to 0.5 micron acicular crystals which form
each composite particle

TYPICAL CHEMISTRY

Si, ppm	3200	< 50
Al, ppm	4000	< 20
P, ppm	1700	< 30
S, ppm	NT	<100
Cl, ppm	NT	<210
Total Other Impurities, ppm	3100	<185
Package Size	100 Lbs.	25 Kg

TAM offers two electronic grades of TiO₂ to meet your demands:

HG - for Dielectric Compositions

HP - for the high purity demands of a typical Barium
Titanate based PTC Composition

Table AII. Analysis of Tantalum Pentoxide

HERMANN C. STARCK BERLIN GMBH & CO. KG																																																		
WERKSPRÜFZEUGNIS/ WORKS REPORT Nach DIN 50049 2.3/acc. DIN 50049 2.3		Nr./No.: 14 03977/2 SM 120 Bearbeiter/Editor: Geng																																																		
Kunde/Customer: DOW Chemicals U S A Bestell Nr./Order No.: S-6286 P.O. 001M3322765 Bestell-Datum/Date of Order:		Produkt/Product: Tantalum Pentoxide Ta205 standard optical grade Menge/Quantity: 5 lbs = 2,268 kgs Lot.-Nr./Lot No.: 848/6																																																		
Analysenergebnisse/Analytical Results:																																																				
<table border="0"> <tr> <td>Ta205</td> <td>min.</td> <td>99,95 %</td> <td rowspan="15" style="vertical-align: middle; text-align: center;"> 14 03977/2 SM 120 Geng </td> </tr> <tr> <td>Nb</td> <td><</td> <td>50 ppm</td> </tr> <tr> <td>Al, Mo</td> <td>max.</td> <td>3 ppm</td> </tr> <tr> <td>B</td> <td>max.</td> <td>0,5 ppm</td> </tr> <tr> <td>Bi, Co, Cr, Cu, F,</td> <td></td> <td></td> </tr> <tr> <td>K, Mn, Na, Ni,</td> <td></td> <td></td> </tr> <tr> <td>Pb, Sn, V</td> <td>max.</td> <td>1 ppm</td> </tr> <tr> <td>Ca, Fe, Mg,</td> <td></td> <td></td> </tr> <tr> <td>Rare Earth tot.</td> <td>max.</td> <td>2 ppm</td> </tr> <tr> <td>W</td> <td>max.</td> <td>4 ppm</td> </tr> <tr> <td>S</td> <td>max.</td> <td>5 ppm</td> </tr> <tr> <td>Ti</td> <td>max.</td> <td>6 ppm</td> </tr> <tr> <td>Zr</td> <td>max.</td> <td>8 ppm</td> </tr> <tr> <td>Si</td> <td>max.</td> <td>15 ppm</td> </tr> <tr> <td>Cl</td> <td>max.</td> <td>300 ppm</td> </tr> <tr> <td>Loss on Ignition</td> <td>max.</td> <td>0,03 %</td> </tr> </table>				Ta205	min.	99,95 %	14 03977/2 SM 120 Geng	Nb	<	50 ppm	Al, Mo	max.	3 ppm	B	max.	0,5 ppm	Bi, Co, Cr, Cu, F,			K, Mn, Na, Ni,			Pb, Sn, V	max.	1 ppm	Ca, Fe, Mg,			Rare Earth tot.	max.	2 ppm	W	max.	4 ppm	S	max.	5 ppm	Ti	max.	6 ppm	Zr	max.	8 ppm	Si	max.	15 ppm	Cl	max.	300 ppm	Loss on Ignition	max.	0,03 %
Ta205	min.	99,95 %	14 03977/2 SM 120 Geng																																																	
Nb	<	50 ppm																																																		
Al, Mo	max.	3 ppm																																																		
B	max.	0,5 ppm																																																		
Bi, Co, Cr, Cu, F,																																																				
K, Mn, Na, Ni,																																																				
Pb, Sn, V	max.	1 ppm																																																		
Ca, Fe, Mg,																																																				
Rare Earth tot.	max.	2 ppm																																																		
W	max.	4 ppm																																																		
S	max.	5 ppm																																																		
Ti	max.	6 ppm																																																		
Zr	max.	8 ppm																																																		
Si	max.	15 ppm																																																		
Cl	max.	300 ppm																																																		
Loss on Ignition	max.	0,03 %																																																		
Bemerkungen/Remarks: "Complies With Inspection Certificate 3.1. B per DIN 50049 April 1992"																																																				
HERMANN C. STARCK BERLIN GmbH & Co. KG Niederlassung Lauenburg Datum/Date: 06/24/92/UM AZE1026 Leiter Kontrolle/Works Inspector																																																				

APPENDIX B: SLIP PREPARATION AND CASTING EXAMPLE

Batch Recipe - Titania with 5 mole % Tantalum Pentoxide

514.65 g TiO_2
149.88 g Ta_2O_5
210 ml deionized water
11 ml 7 weight % ammonium hydroxide solution
1 ml saturated citric acid solution

Processing Directions

1. Add TiO_2 powder, then Ta_2O_5 powder. Starting attritor speed should be slow and gradually increased to about 180 rpm at completion of powder additions. This will take approximately 1 hr 45 min. Gradually inject an additional 4 ml of ammonium hydroxide solution and 0.4 ml of citric acid solution along with the powder.
2. Increase attritor speed to 200 rpm once all powder is in.
3. Begin adding more deflocculant after 3 hours. Between 3 and 8 hours of attrition time, add 3 ml of ammonium hydroxide solution and 0.3 ml citric acid solution.
4. At the end of the work day (8 hours), add 3 ml ammonium hydroxide solution and 0.2 ml citric acid solution.
5. The next morning, add 0.1 ml citric acid solution and enough ammonium hydroxide solution to adjust the pH to at least 8 (= 1 ml).
6. Viscosity should be approximately 50 mPas (spindle 2, 60 rpm) as tested with the Brookfield Digital Viscometer.
7. Cast for 1 hr 15 min. Final sintered thickness will be approximately 3.5 mm. If the viscosity is higher than 50 mPas, reduce casting time slightly.

END

**DATE
FILMED**

6 / 10 / 93