DOE/PC/92543--T1

doeqtr.93/#9

DOE/PC: DE-FG22-92PC92543

MICRO-AGGLOMERATE FLOTATION FOR DEEP CLEANING OF COAL

Quarterly Progress Report: September 30 - December 31, 1992

by

DOE/PC/92543--T1

S. Chander
R. Hogg

DE93 009702

January 1993

Work Performed Under Contract No.

For

U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, PA

by

Penn State University
University Park, PA 16802

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>Page</u>
OBJECTIVES	1
Introduction	1
Task 1. Interfacial Studies	2
Task 2. Emulsification	3
Task 3. Agglomerate Growth and Structure	3
Task 4. Agglomerate Flotation	4
 PROJECT STATUS	 4
Sample Procurement and Preparation	4
Task 1. Interfacial Studies	4
Task 2. Emulsification	5
Task 3. Agglomerate Growth and Structure	5

OBJECTIVES

The goals of this research program are to demonstrate the technical and economic feasibility of a micro-agglomerate flotation process and to establish the essential criteria for reagent selection and system design and operation.

1. Introduction

The development of practical technologies for the deep cleaning of coal has been seriously hampered by the problems of carrying out efficient coal/mineral separations at the very fine sizes (often finer than 10 μm) needed to achieve adequate liberation of the mineral matter from the coal matrix. It is generally recognized that surface-based separation processes such as froth flotation or selective agglomeration offer considerable potential for such applications but there remain many problems in obtaining the required selectivity with acceptable recovery of combustible matter. In froth flotation, selectivity is substantially reduced at fine sizes due, primarily, to overloading of the froth phase which leads to excessive carryover of water and entrained mineral matter. Oil agglomeration, on the other hand, can provide good selectivity at low levels of oil addition but the agglomerates tend to be too fragile for separation by the screening methods normally used. The addition of larger amounts of oil can yield large, strong agglomerates which are easily separated but the selectivity is reduced and reagent costs can become excessive.

We are investigating the use of a hybrid process - Micro-agglomerate flotation - which is a combination of oil-agglomeration and froth flotation. The basic concept is to use small quantities of oil to promote the formation of dense

micro-agglomerates with minimal entrapment of water and mineral particles, and to use froth flotation to extract these micro-agglomerates from the water/dispersed-mineral phase. Since the floating units are agglomerates (about 30-50 μm in size) rather than individual coal particles (1-10 μm) the problems of froth overload and water/mineral carryover should be significantly alleviated.

Micro-agglomerate flotation has considerable potential for the practical deep cleaning of coal on a commercial scale. In principle, it should be possible to achieve both high selectivity and high yield at reasonable cost. The process requires only conventional, off-the-shelf equipment and reagent usage (oil, surfactants, etc.) should be small. There are, however, complications. The process involves at least five phases: two or more solids (coal and mineral), two liquids (oil and water) and one gas (air). It is necessary to maintain precise control over the chemistry of the liquid phases in order to promote the interfacial reactions and interactions between phases necessary to ensure selectivity. Kinetics as well as thermodynamic factors may be critical in determining overall system response.

The research program has been organized into several specific tasks as indicated below.

Task 1. Interfacial Studies

In order to provide a rational basis for reagent selection, fundamental studies of the various interfaces involved in Micro-Agglomerate Flotation are being conducted. In particular, data are being obtained on:

- liquid/air and liquid/liquid interfacial tensions for aqueous solution/hydrocarbon systems.

- solid/liquid/air and solid/liquid/liquid contact angles for coals and important minerals (quartz, pyrite, etc.).

Task 2. Emulsification

The emulsification of oil in the presence of fine particles plays a critical role in the development of micro-agglomerate properties and in the rejection of pyritic sulfur and ash during agglomerate formation. The process is being investigated by measurement of emulsion droplet size distributions in agitated vessels of standard design. The effects of:

- coal type (especially hydrophobicity)
- surfactant type and concentration
- hydrodynamics

are of particular concern.

Task 3. Agglomerate Growth and Structure

In order to achieve the degree of selectivity required for effective deep cleaning of fine coal it is desirable to produce agglomerates which are large enough to be separated from the dispersed, refuse material and have sufficiently high density to minimize the inclusion of water and dispersed mineral particles. Studies of size/density relationships for oil-agglomerated fine coal are an important part of the research program. The role of hydrodynamics in agglomerate densification is of particular interest.

Task 4 - Agglomerate Flotation

The final separation of selectively aggregated fine coal particles from mineral matter is to be achieved using froth flotation. Standard procedures for flotation testing are being used to evaluate the floatability of micro-agglomerates formed under various conditions. Specific studies being carried out include determination of the effects of micro-agglomerate size and structure on the kinetics of flotation and evaluation of the potential for further cleaning of the floated material in multi-stage flotation circuits.

PROJECT STATUS

Sample Procurement and Preparation

Three coals were identified and two samples, one from the Pittsburgh seam and the other from the Illinois #6 seam, have been procured. The Pittsburgh seam coal has been crushed and ground to -8 Mesh and stored under argon.

Task 1. Interfacial Studies

A Wilhelmy plate apparatus using a Cahn microbalance, Model 2000, has been setup to determine surface tension at liquid/air and liquid/liquid interfaces. Measurements were made in the presence of an anionic surfactant, Aerosol-OT. This surfactant was chosen because of its emulsification characteristics and the fact that it was available both in water-soluble and oil-soluble forms.

Previously, we have measured air-water contact angles of coal particles with the interface-partitioning method developed in our laboratories. This method was used to determine the contact angle of Pittsburgh seam coal particles. Preliminary

measurements gave a water/air contact angle of 44° with a standard deviation of 7° . The method is being refined for measurements at oil-water interface. Once the technique is perfected it will be used to measure contact angles in the presence of surfactants.

Task 2. Emulsification

The apparatus for measurement of droplet size distribution of emulsions was modified. A sample of the emulsion flows through the observation cell of a Malvern, Model 2600c, particle size analyzer. The apparatus will be used to measure droplet size distribution of oil in the presence of various surfactants.

Task 3. Agglomerate Growth and Structure

To produce micro-agglomerates under controlled hydrodynamic conditions a one liter cell of 'standard geometry' has been fabricated. The dynamics of micro-agglomerate formation will be investigated using size distribution measurements on agglomerates produced in the standard mixing tank. The effect of chemical conditions and hydrodynamic factors on the rate of agglomerate size and composition will be determined.

END

**DATE
FILMED**

4 / 14 / 93