27.
11/28/78
24 7115

SAND78-1256

UNLIMITED RELEASE

MASTER

A MODEL FOR ESTIMATING THE EFFECTS OF SURFACE
ROUGHNESS ON MASS EJECTION FROM SHOCKED MATERIALS

J. R. ASAY, L. D. BERTHOLF

Prepared by Sandia Laboratories, Albuquerque, New Mexico 87115
and Livermore, California 94550 for the United States Department of
Energy under Contract AT(29-1)-789

PRINTED OCTOBER 1978

Sandia Laboratories

Issued by Sandia Laboratories, operated for the United States Energy Research & Development Administration by Sandia Corporation.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research & Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Printed in the United States of America

Available from
National Technical Information Service
U. S. Department of Commerce
5285 Port Royal Road
Springfield, VA 22161

Price: Printed Copy \$5.25; Microfiche \$3.00

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

A MODEL FOR ESTIMATING THE EFFECTS OF
SURFACE ROUGHNESS ON MASS EJECTION FROM SHOCKED MATERIALS

J. R. Asay
Thermomechanical & Physical Research Division 5534

L. D. Bertholf
Computational Physics & Mechanics Division I, 5531
Sandia Laboratories, Albuquerque, New Mexico 87185

ABSTRACT

A statistical model is presented for estimating the effects of surface roughness on mass ejection from shocked surfaces. In the model, roughness is characterized by the total volume of defects, such as pits, scratches and machine marks, on a surface. The amount of material ejected from these defects during shock loading can be estimated by assuming that jetting from surface depressions is the primary mode of ejection and by making simplifying assumptions about jetting processes. Techniques are discussed for estimating the effects of distribution in defect size and shape, and results are presented for several different geometries of defects. The model is used to compare predicted and measured ejecta masses from six different materials. Surface defects in these materials range from pits and scratches on polished surfaces to prepared defects such as machined or porous surfaces. Good agreement is achieved between predicted and measured results, which suggests general applicability of the model.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

leg

CONTENTS

I. INTRODUCTION.....	6
II. MODEL FOR MASS EJECTION FROM SURFACE DEPRESSIONS.....	9
Model Development.....	9
Jetting from Uniform Cavities.....	15
Jetting Factor.....	18
Effect of Defect Distribution.....	26
Effect of Shock Pressure.....	30
Effect of Shock Risettime.....	32
Application.....	38
Limitations of the Model.....	44
III. CONCLUSION.....	48
IV. ACKNOWLEDGEMENTS.....	50
REFERENCES.....	51
APPENDIX A - Estimation of the Viscosity of Aluminum from Jetting	
Experiments.....	53

LIST OF FIGURES

- Figure 1. Idealized defects normally observed on surfaces. Conical or hemispherical defects are often observed on polished surfaces and result from removal of impurities or indentation. Linear defects, such as wedge-shaped cavities, arise from scratches or machining operations. Detailed examination reveals that these various defects may be flat-bottomed.
- Figure 2. Distribution functions which describe variations in defect depth and angle. (a) $\eta(x)$ is a normalized function which describes variations from the average defect depth, $\bar{x}$. (b) $\eta(\theta)$ accounts for variations in angle and is approximated by a triangular function.
- Figure 3. Experimental technique used to measure jet mass and velocity from linear wedge-shaped cavities on aluminum. Microjets produced by shock reflection at the surface are collected with a witness foil. Time-resolved interferometer measurements of the foil velocity allow determination of jet mass and velocity.
- Figure 4. Numerical simulation of microjetting from a 90° wedged cavity in aluminum. A 30 GPa shock is initiated in the first frame, and the interaction of the shock with the groove develops a well-defined jet, as demonstrated in succeeding frames.
- Figure 5. Determination of the jetting factor for linear, wedge-shaped cavities. Numerical calculations were performed for a 30 GPa shock in aluminum incident on cavities which were 0.05 mm deep with cavity angles of $15 - 90^\circ$ and spaced 0.125 mm apart. For the larger angles, the total groove width and separation was

held constant at 0.1 mm and 0.125 mm, respectively, and the depth was varied. The experimental data for aluminum were also obtained for 30 GPa shock wave incidence on cavities of the same nominal dimensions. Eighty-eight GPa shock waves were used to shock surfaces on copper-gold which contained wedge-shaped cavities approximately 0.05 mm deep and separated by 0.125 mm.

Figure 6. Effect of yield strength on mass ejection from wedge-shaped cavities. (a) The incidence of 4.5 and 30 GPa shock waves on 90° wedge-shaped cavities in aluminum was investigated. The static yield strength of aluminum was assumed to be 0.3 GPa. (b) Ejecta mass and maximum ejecta velocity as a function of the ratio of yield strength to shock pressure. Both of these quantities have been normalized to their values corresponding to zero yield strength ($Y = 0$).

Figure 7. A wave of amplitude P with a finite width is shown incident on a cavity of depth x .

Figure 8. (a) Experimental technique for producing non-shock loading of a free surface. Experiments were conducted on 6061-T6 aluminum specimens for an impact stress of about 21 GPa. The ramp generator was a glass ceramic (Corning Pyroceram). (b) Ejecta mass as a function of wave risetime for the experiment depicted in (a). Time and mass resolutions are indicated by the dashed lines.

Figure 9. Predicted and measured normalized ejecta mass as a function of effective defect volume. Both normalized mass and defect volume are defined per unit area. Parameters for the experimental data are given in Table IV.

I. INTRODUCTION

There has been considerable interest in recent years regarding the response of surfaces to high-pressure shock loading. One aspect of this concerns the stability of surfaces during dynamic loading. This question has been considered in numerous theoretical and experimental studies.¹⁻⁴ Another aspect relates to the ejection of debris in the form of small particles or vaporized products from surfaces which are loaded with high-amplitude shock waves. This effect has been observed and quantified in several different high-pressure surface response experiments⁵⁻⁷. These investigations have also allowed identification of several material and surface properties which are important to the ejection process. Surface roughness is observed to be the most important single parameter influencing mass ejection from surfaces, which follows from the strong correlation observed between roughness and ejecta mass.⁷

Although these earlier studies have identified parameters of importance and have established approximate correlations between surface finish and ejecta mass, analytic techniques have not been previously developed for making quantitative estimates of material ejected from a surface during shock loading. The problem is complicated by the wide variety of defect geometries which are generally present on a surface, and the necessity to describe how each of these ejects mass. However, there is considerable interest in developing methods for predicting ejecta mass for arbitrary surface conditions from the point of view of either minimizing the effect or of understanding how it affects other physical phenomena. For these reasons, an analytic technique has been developed for making quantitative estimates of ejecta mass for arbitrary surface conditions and arbitrary materials.

The model which has been developed for predicting ejecta mass is based on several assumptions. The basic assumption is that mass ejection occurs primarily by jetting during shock wave reflection from cavities on a surface. These depressions are usually in the form of pits, scratches or machine marks. The roughness of the surface is characterized in the model by the total volume of defects per unit area on the surface. By making simplifying approximations of jetting phenomena, it is possible to develop statistical methods for relating defect volume to the amount of material ejected from the surface. The statistical approach accounts approximately for the variations in defect depth and geometry, which are expected for imperfections usually present on a surface.

In this paper, several different defect geometries have been considered. These include defects in the form of grooves which would describe machined surfaces or surfaces containing scratches, and conical defects which approximate pits that often result from polishing operations. It is found that these different cases can be conveniently treated by introducing a parameter, referred to as the jetting factor, which relates jet mass to the cavity volume of the defect. This factor depends on defect geometry and can be evaluated from experimental or numerical methods. Numerical calculations have been used in the present work to evaluate the jetting factor for several different geometries. For 28 different defect geometries, this factor is found to be nearly unity, which implies that the volume of material in a jet from a cavity is nearly equal to the cavity volume.

Methods are discussed for estimating the total defect volume on a surface. For machined surfaces, this is easily accomplished from profile measurements of the surface. For surfaces containing arbitrary defects,

the defect volume can be estimated from either visual observations of the surface or through automated scanning techniques. Resulting uncertainties in defect volume vary with the surface conditions and how well they are characterized, but are expected to be no more than a factor of four in the worst cases. However, it should be possible to characterize the defect volume of machined surfaces with an uncertainty less than 50%.

The model has been used to predict ejecta masses for several materials which have been studied experimentally. These materials contain surface defects ranging from naturally occurring imperfections such as pits and scratches to prepared defects such as machine marks and porous surfaces. Very good agreement is obtained between predicted and measured results, which suggests general applicability of the model.

A discussion is also presented regarding an extension of the model to predict a lower limit for the defect sizes which cause mass ejection. It is expected on physical grounds that a sufficiently small imperfection should not cause mass ejection during shock loading, and this hypothesis is supported by experimental evidence. Thus, an estimate of the lower limit in defect size which causes ejection is presented in terms of material and shock wave properties.

In the next section, the model is formulated and applied to several specific cases. In following sections, determination of the jetting factors is discussed, and the model is applied to experimental results obtained for several different materials. Finally, we discuss limitations of the technique.

II. MODEL FOR MASS EJECTION FROM SURFACE DEPRESSIONS

In order to develop a model for estimating how surfaces eject mass under shock loading, it is necessary to know the details of the ejection process. There is substantial available evidence which indicates that microjetting from surface depressions occurs during shock loading of material surfaces and is the main source of ejection in most cases. If depressions are assumed to be the major source of ejection, accurate description of the surface roughness and knowledge of jetting processes would be sufficient to predict the amount of material ejected from the surface. Clearly, this procedure would become untenable if every defect on the surface which contributes to ejection must be described. For this reason, it is necessary to employ statistical treatments of ejection from arbitrary defect sizes, using some basic assumptions of jetting processes.

Model Development

Processes which produce jets during shock wave interactions with surface cavities are complicated by the fact that jet masses and velocities depend on several properties of the material, cavity and the loading history. It would be unrealistic to attempt a detailed description of all properties influencing jet formation. To be useful for predicting mass ejecta from arbitrary materials and surfaces, a model should contain a minimum number of parameters. Furthermore, parameters which are included in the material description should be easily determined and as general as possible. With these requirements in mind, three simplifying assumptions have been made regarding jetting processes. These are (i) that the mass produced in a jet by interaction of a shock wave with a surface cavity is proportional

to the volume of the depression, (ii) that the mass in a jet is proportional to the initial density of the material containing the defect and independent of any other material property, and (iii) that the mass in a jet produced by shock-loading of depressions is independent of shock pressure.

Although these assumptions appear to be restrictive, there is sufficient evidence which indicates that resulting errors are minimal in most cases. For example, the first assumption implies that geometrical scaling applies to jetting from surface depressions. Scaling has not been demonstrated rigorously for jetting from surface depressions of arbitrary size. However, recent experimental and numerical investigations indicate that cavity volume scaling does apply to jetting from wedge-shaped depressions in aluminum down to depths that are as small as 50 μm .^{6,8,9} This dimension is on the order of (although somewhat higher than) the defect size normally encountered during surface preparation, so that the first assumption should be a reasonable approximation. Limitations to the applicability of this assumption will be discussed more completely in a following section.

The remarkable success achieved with jetting theories based on incompressible flow provides motivation for the second assumption. It has been found that both jet masses and velocities from lined shaped charges can be accurately predicted with theories based on steady material flow and material incompressibility.¹⁰⁻¹² Thus, it would be expected that errors resulting from compressibility effects would not be large in most cases. By the second assumption, it is only necessary to specify the initial material density, and by eliminating properties, such as equation of state information, the model is considerably simplified.

The third assumption is that shock pressure does not influence jet mass. This is observed to be a good approximation in numerical simulations

of jet formation from wedge-shaped cavities of aluminum,⁸ provided that the shock amplitude is much larger than the yield strength of the material, but not sufficient to initiate free surface melting. Previous experimental work on lead^{6,7} indicates that an enhancement in shock-induced surface ejecta may occur for pressures sufficient to cause melting under plane loading and unloading conditions. However, we will assume that both yield strength and melting effects are not important during shock loading. This is not a serious limitation, since shock pressures of several tens of GPa are usually necessary to induce melting and yield strengths are typically less than 1 GPa.

Using these three assumptions, it is possible to develop some general conditions for jetting from surface depressions. As mentioned earlier, several types of depressions may occur on a surface. Some idealized geometries which approximate typical surface defects are depicted in Figure 1. Imperfections which have shapes similar to those illustrated in the figure usually occur as a result of machining or polishing operations. If a shock wave reflects from a surface containing such defects, high velocity jets from the surface will be formed. In general, the maximum velocity of these jets will be on the order of twice the free surface velocity.

The total mass contained in a jet is defined as the amount of material traveling faster than the free surface velocity obtained under plane loading of the surface (in the absence of defects). From the first two assumptions the total jet mass, m_j , is proportional to the volume of the cavity, v_d , and the initial density, ρ , of the material containing the cavity;

$$m_j \propto \rho v_d \quad . \quad (1)$$

Figure 1. Idealized defects normally observed on surfaces. Conical or hemispherical defects are often observed on polished surfaces and result from removal of impurities or indentation. Linear defects, such as wedge-shaped cavities, arise from scratches or machining operations. Detailed examination reveals that these various defects may be flat-bottomed.

The proportionality constant will generally be a function of the cavity geometry and perhaps the material. From assumption (ii) we will ignore the effect of different materials and define the constant of proportion as

$$\mathcal{R}(\theta) \equiv \frac{m_j}{\rho v_d} , \quad (2)$$

where θ represents the cavity geometry. $\mathcal{R}$ will be referred to as the jetting factor in later discussions.

For a surface containing several depressions, the total mass ejected per unit area, A , of the surface will be a sum of the individual contributions,

$$m_T = \Sigma m_j / A . \quad (3)$$

Furthermore, it is expected that there will be a distribution in geometry, size and angular dependence for the defects. Distributions in geometry are embodied in the jetting factor and will be considered later. For a given geometry, it is then only necessary to consider distributions in defect size and angle. This problem is conveniently treated with distribution functions, which are identified here as $\eta(x)$ and $\eta(\theta)$, where x is cavity depth and θ is half-angle (see Fig. 1). It is further assumed that these functions are normalized,

$$\int_D \eta(\tau) d\tau = 1 , \quad (4)$$

where integration is over the relevant domain of x or θ . For a distribution of surface defects, we will assume that Equation (3) can be generalized to

$$\mathfrak{m} = \int_0^{\pi/2} \int_0^{\infty} \mathfrak{R}(\theta) \eta(\theta) \eta(x) f(x, \theta) dx d\theta . \quad (5)$$

The quantity $\mathfrak{m}$ is the normalized ejecta mass (jet volume) which is defined as

$$\mathfrak{m} = \frac{m_T}{\rho} . \quad (6)$$

The individual defect volume is given in general as

$$v_d = f(x, \theta) .$$

For defects with an angular dependence, θ is the half angle and is assumed to range from 0 to $\pi/2$ (only one angular dependence is assumed here for simplicity). Since the total mass ejected, m_T , is defined per unit area, $\mathfrak{m}$ will have dimensions of length. Note that Equation (5) is independent of material properties and depends only on properties of the surface. The actual ejecta mass for a given material is determined from Equation (6).

In order to proceed further, it is necessary to define the functions $\eta(x)$, $\eta(\theta)$ and $f(x, \theta)$. This is generally not possible without specific information about the surface. However, several cases will be treated which illustrate the method and serve as approximations for different surface conditions. A Gaussian distribution will be used to approximate the variation in defect depth, x ,

$$\eta(x) = \frac{\eta_0}{\sigma\sqrt{2\pi}} \exp -(x - \bar{x})^2/2\sigma^2 , \quad (7)$$

where η_0 is the total number of defects per unit area on the surface, $\bar{x}$ is the mean depth and σ is the standard deviation from the mean. This

function is illustrated in Figure 2a. It would also be expected that a Gaussian distribution would approximate the angular distribution of cavities. For the geometries considered here, we have not been able to obtain analytic closed-form solutions for ejecta mass, assuming Gaussian distributions in angle. In order to make the analysis tractable, a piece-wise linear distribution was used to approximate a Gaussian function, as illustrated in Figure 2b. The approximate distribution becomes

$$\eta(\theta) = \begin{cases} 0 & \theta < \bar{\theta} - \delta\theta \\ \frac{1}{\delta\theta^2}(\theta - \bar{\theta} + \delta\theta) & \bar{\theta} - \delta\theta < \theta < \bar{\theta} \\ \frac{1}{\delta\theta^2}(\delta\theta + \bar{\theta} - \theta) & \bar{\theta} < \theta < \bar{\theta} + \delta\theta \\ 0 & \bar{\theta} + \delta\theta < \theta \end{cases} \quad (8)$$

where $\bar{\theta}$ is the mean defect angle and $\delta\theta$ is the maximum deviation from the mean.

Equations (5) through (8) allow estimation of the total ejecta mass from shocked surfaces which contain a distribution of depressions. Some simple geometries without distribution effects will be illustrated first. The distribution functions (7) and (8) will then be used to estimate errors associated with these results. Finally, Equation (5) will be used to compare experimental data obtained on several different materials to illustrate the applicability of the approach.

Jetting from Uniform Cavities

In this section we will consider the total mass ejected from a surface containing cavities of uniform geometry. The case for conical cavities will be considered in detail and the results for other common geometries will be summarized in a table.

(a)

(b)

Figure 2. Distribution functions which describe variations in defect depth and angle. (a) $\eta(x)$ is a normalized function which describes variations from the average defect depth, $\bar{x}$. (b) $\eta(\theta)$ accounts for variations in angle and is approximated by a triangular function.

For a surface containing an areal density, η_0 , of right conical pits with fixed depth $\bar{x}$ and fixed apex angle $\bar{\theta}$ (half the included angle), the distribution functions are delta functions,

$$\eta(x)\eta(\theta) = \eta_0 \delta(x - \bar{x}) \delta(\theta - \bar{\theta}) .$$

Equation (5) becomes

$$f(\bar{x}, \bar{\theta}) = \frac{\pi}{3} \bar{x}^3 \tan^2 \bar{\theta} , \quad (9)$$

and

$$m = \frac{\pi}{3} \eta_0 \mathcal{R}(\bar{\theta}) \bar{x}^3 \tan^2 \bar{\theta} . \quad (10)$$

In order to determine the total ejecta mass, it is then only necessary to specify the material density and the jetting factor $\mathcal{R}(\theta)$ for conical pits.

Equation (10) can be put in a form which is more amenable to automated measurement of the total defect volume on a surface. The area, a_d , projected on the surface by an individual cavity is

$$a_d = \pi \bar{x}^2 \tan^2 \bar{\theta} , \quad (11)$$

and the total relative surface area, a_r , occupied by all defects is defined as

$$\begin{aligned} a_r &= \iint a_d \eta(x) \eta(\theta) dx d\theta \\ &= \eta_0 a_d . \end{aligned} \quad (12)$$

In terms of these definitions, Equation (10) becomes

$$m = \frac{1}{3} \mathcal{R}(\bar{\theta}) \bar{a}_r \bar{x} \quad (13)$$

Automated scanning of surface photographs can be used to determine $\bar{a}_r$. It is then only necessary to measure the depth, $\bar{x}$, of defects to determine the normalized ejecta mass (once the jetting factor is known).

This procedure is easily extended to other cavity geometries. In Table I we have summarized several different geometries. In particular, note the result for sawtooth, wedge-shaped cavities which approximates machined surfaces. In this case, the normalized ejecta mass is simply one-half the product of the jetting factor and the peak-to-valley separation $\bar{x}$. This result is especially convenient since surface profile measurements can be used to determine $\bar{x}$ from "RMS" (root mean square deviation from centerline) or "AA" (arithmetic average deviation from centerline) specifications. For wedge-shaped grooves these values are related as

$$\bar{x} \doteq 3.5 X_{\text{RMS}} , \quad (14)$$

and

$$\bar{x} = 4X_{\text{AA}} . \quad (15)$$

When the jetting factor for machining marks is specified, the RMS or AA surface specifications can be used to estimate the defect volume and thus the ejecta mass.

Jetting Factor

In order to use the relations developed for predicting ejecta mass, it is necessary to determine the jetting factor, $\mathcal{R}$, for each case. Since the jetting factor is defined as the ratio of ejecta mass to the product of the initial density and the defect volume (Equation 2), it could be determined experimentally by measuring ejecta from known defects

TABLE I

DEFECT VOLUME FOR DIFFERENT CAVITY GEOMETRIES

Cavity Type	Individual Cavity Volume, $f(x,y)^a$	Relative Cavity Surface Area ^b , a_r	Total Cavity Volume ^c
Conical	$1/3 \pi x^3 \tan^2 \theta$	$\eta_0 \pi x^2 \tan^2 \theta$	$1/3 a_r x$
Hemispherical	$2/3 \pi x^3$	$\eta_0 \pi x^2$	$2/3 a_r x$
Flat-Bottom Conical	$1/3 \pi \tan^2 \theta \left[\left(x + \frac{y}{2 \tan \theta} \right)^3 - 1/8 y^3 \tan \theta \right]$	$\eta_0 \pi (x \tan \theta + y/2)^2$	$1/3 a_r x \left[1 + \frac{1/2 y (x \tan \theta + y/2)}{(x \tan \theta + y/2)^2} \right]$
Wedge-shaped Plane Grooves ^d	$x^2 \tan \theta$	$2 \eta_0 x \tan \theta$	$1/2 a_r x$
Sawtooth Parallel Grooves ^d	$x^2 \tan \theta$	1	$1/2 x$
Flat-Bottom Parallel Grooves ^d	$x^2 \tan \theta + xy$	$\eta_0 [y + 2x \tan \theta]$	$a_r x \left[1 - \frac{x \tan \theta}{2x \tan \theta + y} \right]$
Cylindrical Parallel Grooves ^d	$1/2 \pi x^2$	$2 \eta_0 x$	$\frac{\pi}{4} a_r x$

^a Cavity dimensions are defined in Figure 1. Note that θ is the cavity half-angle.

^b The relative cavity surface area, a_r , is defined assuming a uniform surface density, η_0 , of cavities.

^c Normalized ejecta mass is defined as the product of the jetting factor and total cavity (defect) volume.

^d Cavity volume for linear cavities is defined per unit length.

on the surface. Techniques have been previously reported⁵⁻⁹ for measuring ejecta from well-defined cavities and an experimental method for measuring jet masses from wedge-shaped linear cavities is reproduced in Figure 3. Time-resolved measurements of the particle velocity imparted to a collecting foil by multiple jet impact allow determination of the total mass ejected from the surface by jetting. From knowledge of the cavity dimension and separation, it is possible to determine the jet mass per cavity and thus the jetting factor.

An alternate procedure is to use numerical simulation of shock wave interaction with a well-defined cavity to determine the jetting factor. This procedure has been previously described^{8,9,13} and is illustrated in Figure 4. For this example, a two-dimensional wave propagation code (CSQ)¹⁴ was used to simulate a 30 GPa shock incident on a 90° wedge-shaped cavity in aluminum. Interaction of the shock with the cavity produces a well-defined jet, which is apparent in the later frames. The total jet mass is defined in the calculations as the total amount of material traveling faster than the free surface velocity corresponding to plane surfaces. Since the cavity volume, v_d , is known, the jetting factor corresponding to 90° grooves can be determined from Equation (2).

The jet masses determined either experimentally or numerically are influenced by boundary effects near the free surface. That is, a surface may not maintain a definite boundary when shocked to high pressures, so that actual definition of ejecta mass may be influenced by experimental or numerical resolution. Although this effect is a problem in some cases, consistency in determining ejecta mass can be maintained by defining ejecta as the amount of material traveling faster than the free surface velocity obtained for shock loading of planar surfaces.

Figure 3. Experimental technique used to measure jet mass and velocity from linear wedge-shaped cavities on aluminum. Microjets produced by shock reflection at the surface are collected with a witness foil. Time-resolved interferometer measurements of the foil velocity allow determination of jet mass and velocity.

Figure 4. Numerical simulation of microjetting from a 90° wedged cavity in aluminum. A 30 GPa shock is initiated in the first frame, and the interaction of the shock with the groove develops a well-defined jet, as demonstrated in succeeding frames.

Clearly, it would not be feasible to determine jetting factors experimentally for all of the different geometries which describe typical defects on a surface. A more realistic approach is to use numerical simulation of jetting for different cavity geometries. This observation has been verified approximately by experimental and numerical simulation of jetting from grooved surfaces of aluminum which were shocked to 30 GPa. The grooves were in the form of parallel wedge-shaped grooves that were approximately 0.05 mm deep and separated by about 0.125 mm (see Figure 3). Excellent agreement between the calculated and experimental mass velocity profiles have been previously reported.^{8,9,13} Additional comparisons are given in Figure 5 in terms of the jetting factor. Generally, good agreement is obtained between the two determinations of ejecta mass for total groove angles to about 90°. This agreement implies that either numerical or experimental methods can be used to determine jetting factors for arbitrary geometries.

Experimental measurements of mass ejecta from grooved surfaces (also 0.05 mm deep) of copper-gold (50% Cu by volume) alloy are also shown in the figure. The agreement in the results obtained for the two materials indicates that our representation of the material by a single parameter (ρ) is reasonable. This simplifies the determination of jetting factors, as indicated earlier, since it is not necessary to study jetting for both different cavity geometries and different materials.

Jetting from cavities with several different geometries was studied with numerical techniques. The results of these calculations are summarized in Table II, with the relevant cavity properties defined in Figure 1. The boundary conditions shown in Figure 1 were chosen to represent either isolated cavities (transmissive boundaries) or periodic cavities (reflective boundaries). In most cases, the difference in jetting factors

TABLE II
APPROXIMATE JETTING FACTORS FOR DIFFERENT GEOMETRIES

Geometry ^a	θ Degrees	Boundary ^b Condition	x μm	D μm	Jetting Factor R
Plane Grooves	7.5	R	50	13.2	1.14
	15	R	50	26.8	0.73
	22.5	R	50	41.4	0.66
	45	R	50	100	0.73
	45 ^c	T	50	100	0.83
	45 ^c	R	62.5	125	0.49
	45 ^c	R	31.25	62.5	0.53
	45 ^c	R	15.75	31.5	0.51
	45 ^d	R	50	110	0.63
	60	R	28.9	100	1.31
	75 ^e	R	13.4	100	2.49
	--f	R	50	100	0.53
	--f	R	20	40	1.00
	--f	T	20	40	1.00
	--f	R	50	40	0.41
	--f	T	50	40	0.43
	--f	R	50	100	0.52
Conical Cavities	7.5	R	50	13.2	1.47
	15	R	50	26.8	0.67
	22.5	R	50	41.4	1.4
	45	R	50	100	1.0
Cylindrical Cavities	--g	R	20	40	1.29
	--g	T	20	40	1.21
	--g	R	50	40	0.68
	--g	T	50	40	1.10
	--g	R	50	100	0.46
	--g	T	50	100	0.73
	--h	R	50	100	0.52

^a Numerical calculations were performed with a two-dimensional wave propagation code, CSQ, for a 30 GPa shock wave incident on cavities in aluminum. In all calculations, the width of the region containing the groove was 125 μm . The groove depth and surface width (see Figure 1) are defined as x and D, respectively.

^b The boundaries of the region containing the groove were either reflecting (R) or transmitting (T). Reflecting boundaries define planes of symmetry and transmitting boundaries correspond to isolated cavities.

^c The grooves are sawtooth in shape.

^d Flat-bottomed cavity.

^e Cylindrical-shaped groove.

^f Square cavity of depth x and width D.

^g Cylindrical-shaped cavity of depth x and diameter D.

^h Hemispherical cavity of radius x.

Figure 5. Determination of the jetting factor for linear, wedge-shaped cavities. Numerical calculations were performed for a 30 GPa shock in aluminum incident on cavities which were 0.05 mm deep with cavity angles of 15 - 90° and spaced 0.125 mm apart. For the larger angles, the total groove width and separation was held constant at 0.1 mm and 0.125 mm, respectively, and the depth was varied. The experimental data for aluminum were also obtained for 30 GPa shock wave incidence on cavities of the same nominal dimensions. Eighty-eight GPa shock waves were used to shock surfaces on copper-gold which contained wedge-shaped cavities approximately 0.05 mm deep and separated by 0.125 mm.

for these two different conditions is minimal to within the accuracy of the calculations. It was found that the accuracy of determining jet mass is fairly sensitive to the effective numerical resolution, which varied for the different cases considered. The influence of numerical resolution on jetting factor is especially evident from the calculations performed on cylindrical cavities with transmittive boundaries. For cavities that were either 20 μm or 50 μm deep, the number of zones used in the CSQ calculation was maintained constant. It was found that the jet mass, and therefore the jetting factor, was about 60% greater for the low resolution (20 μm deep cavity) calculation. This is thought to be an extreme case. However, since the effects of resolution have not been extensively studied in all cases, the jetting factors presented in Table II should be considered approximate.

These jetting factors can be used in the previous formulation to determine ejecta masses. A significant point about the results presented in Table II is that in nearly all cases the jetting factor is within 50% of unity, to within the limitations mentioned above. This implies that the volume of material ejected from the cavity into the jet is nearly equal to the initial volume of the cavity.

Effect of Defect Distribution

In the previous development, it was assumed that all defects present on a surface had a fixed depth $\bar{x}$ and angle $\bar{\theta}$. This will generally not be the case. For example, on machined surfaces, variations will occur in both the depth and angle of machine grooves. For surfaces containing natural defects in the form of pits and scratches arising from polishing operations, variations in depth, angle and geometry will usually be present. With the possible exception of machining marks, diagnostic methods have

not been developed to the point where all variables (such as depth, angle and geometry) of a surface can be accurately specified. It is usually only possible to obtain a reasonable estimate of the average areal density of defects and their average depth. In view of these limitations, the earlier results will be extended to include contributions to mass ejection from shocked surfaces by distributed effects in defect volume. In this development, the variables $\bar{x}$ and $\bar{\theta}$ defined earlier will be interpreted as mean values.

For conical cavities, the individual cavity volume is given by Equation (9). Using Equations (7) and (8) the total normalized ejecta mass is given approximately as

$$\begin{aligned}
 m &= \int_0^{\pi/2} \int_0^{\infty} R(\theta) \eta(\theta) \eta(x) f(x, \theta) dx d\theta \\
 &\doteq \frac{1}{3} \bar{a}_r \bar{x} C(x) C(\theta) \quad , \quad (16)
 \end{aligned}$$

where $\bar{a}_r$ is the projected average relative surface area of defects defined by Equation (12) and $\bar{x}$ is their average depth. Effects of distributed depth and angle are determined by the correction factors $C(x)$ and $C(\theta)$, which are defined as

$$\begin{aligned}
 C(x) &= \frac{\int_0^{\infty} x^3 \eta(x) dx}{\int_0^{\infty} x^2 \eta(x) dx} \quad , \\
 &\doteq 1 + 2\sigma^2/\bar{x}^2 \quad , \quad (17)
 \end{aligned}$$

and

$$C(\theta) = \frac{\int_0^{\pi/2} R(\theta) \tan^2 \theta \eta(\theta) d\theta}{\int_0^{\pi/2} \tan^2 \theta \eta(\theta) d\theta}$$

$$= \overline{R \tan^2 \theta} / \overline{\tan^2 \theta} , \quad (18)$$

where σ is the standard deviation from the mean cavity depth. As shown by Table II, the jetting factor for conical cavities varies by no more than $\pm 50\%$ from unity for a wide range of cavity angles. Because of this, a reasonable estimate of ejecta mass is obtained by using the average value of R for a surface. This approximation offers a considerable simplification in most cases, since distributions in defect angle are usually not known.

Distribution of the cavity depth from the average value causes an increase in ejecta mass (compare Equation (13) with Equations (16-18)). This results because cavities which are deeper than average contribute proportionally more to ejecta mass than smaller ones. Since distribution effects in defect depth can usually be estimated, Equation (16) provides a correction to the earlier result. However, in most cases the correction will be small. For example, if the standard deviation is as large as one-half the mean depth, the correction factor $C(x)$ is about 1.5.

In a similar way, distributed effects can be estimated for the other cavity geometries considered earlier. The defects usually occurring on a surface can be approximated as either conical, wedge-shaped or sawtooth in shape. We have summarized these particular cases in Table III. Note that for machined surfaces, as approximated by sawtooth cavities, the normalized

TABLE III
EFFECTIVE DEFECT VOLUMES

<u>Cavity Type</u>	<u>Effective Defect Volume, V_E^a</u>	<u>Correction Terms^{b,c}</u>	
		$C(x)$	$C(\theta)$
Conical	$1/3 \bar{a}_r \bar{x} C(x) C(\theta)$	$1 + 2\sigma^2/\bar{x}^2$	$\mathcal{R} \tan^2 \theta / \tan^2 \bar{\theta}$
Wedge-shaped	$1/2 \bar{a}_r \bar{x} C(x) C(\theta)$	$1 + \sigma^2/\bar{x}^2$	$\mathcal{R} \tan \theta / \tan \bar{\theta}$
Sawtooth	$1/2 \bar{x} C(x) C(\theta)$	$1 + \sigma^2/\bar{x}^2$	$\mathcal{R} \tan \theta / \tan \bar{\theta}$

a. $\bar{a}_r$ is the average projected relative surface density of defects and $\bar{x}$ is their average depth.

b. σ is the standard deviation of defect depth from the mean $\bar{x}$.

c. The bars denote average values. The jetting factors, $\mathcal{R}$, are given in Figure 5 and in Table II.

ejecta mass is still approximately one-half the average peak-to-valley surface deviation, since the correction terms do not vary significantly for moderate deviations from the mean values.

Table III shows that limitations imposed by distributed effects of size and angle should not be serious in most cases. Because of this, if information is not available about deviations from the mean depth or average angle, the simpler relations presented earlier can be used along with the assumption that $R = 1$ to obtain a good first approximation of ejecta mass. On the other hand, it may be realistic in some cases to estimate the effects of distribution in size and angle in order to improve this estimate.

Effect of Shock Pressure

The assumption that the mass produced in a jet is independent of shock pressure must be qualified. Bertholf⁸ has recently investigated this effect numerically for shock wave incidence on 90° cavities in aluminum. Some of these results are reproduced in Figure 6 and indicate that if the shock amplitude is too small, elastic restoring forces prevent jetting. This effect occurs in materials exhibiting elastic-plastic response by deviatoric stresses which exist near the cavity and impede implosion of the walls and therefore flow of material into the jet. In the figure, the effect of yield strength is illustrated by plotting jet mass and maximum jet velocity versus the ratio of yield strength, Y , to shock pressure, P . In both graphs, the calculated values are compared with those corresponding to zero strength. For initial shock pressures of 4.5 and 30 GPa, these calculations show that yield strength is not important until it is on the order of 0.01 P . For yield stress-to-shock pressure amplitudes (designated by the factor f) of about 0.1, the amount

Figure 6. Effect of yield strength on mass ejection from wedge-shaped cavities. (a) The incidence of 4.5 and 30 GPa shock waves on 90° wedge-shaped cavities in aluminum was investigated. The static yield strength of aluminum was assumed to be 0.3 GPa. (b) Ejecta mass and maximum ejecta velocity as a function of the ratio of yield strength to shock pressure. Both of these quantities have been normalized to their values corresponding to zero yield strength ($Y = 0$).

of ejecta is reduced by 50% from that for zero yield strength. Still higher yield strengths are sufficient to completely suppress jetting. Because of these considerations, the shock strength should be at least an order of magnitude greater than the yield strength of the material to minimize the effects of elastic response. If the shock amplitude is very much smaller than this, the model may give an overestimate of ejecta mass.

There may also be an upper limit to the shock strength which is applicable to the model. Numerical simulations⁸ of shock interaction with grooves indicate that jet mass is not a strong function of shock pressure in the high pressure region. This was found to be the case, even if surface melting occurs during shock loading. However, the calculations show that large density gradients occur in jetted material near the free surface when melting initiates. This effect makes definition of a free surface ambiguous. Therefore, the amount of material "ejected" from the surface may not be well-defined. Experimental results on lead⁶ tend to support this conclusion since a large increase in ejecta mass is observed for ejecta velocities only a few percent greater than the free surface velocity when melting occurs. It is presently not clear whether this observed increase is due to melting itself or is a consequence of experimental resolution. For this reason, the model should be used with caution in regions where surface melting may occur. However, this restriction is usually not severe, since shock pressures of a few tens of GPa are necessary to induce melting.

Effect of Shock Risetime

The first assumption (i) which concerns scaling to arbitrary cavity dimensions may be invalid in some situations. For example, scaling rules would not apply to arbitrary cavity size if a characteristic length or time were associated with jetting. Characteristic dimensions can arise

through rate-dependent processes associated with material response or through characteristic dimensions of the shock itself. For example, it would be expected on intuitive grounds that if the shock risetime is much larger than the transit time across surface defects, the stress gradients necessary to cause jetting would not be present and therefore a jet would not form. This effect can be put on a quantitative basis. Suppose that the stress wave in Figure 6a is of finite width, as shown in Figure 7. We will assume that the stress gradient, $\left(\frac{\partial P}{\partial x}\right)_a$, applied in the vicinity of the surface cavity must exceed a critical value for jetting to occur,

$$\left(\frac{\partial P}{\partial x}\right)_a > \left(\frac{\partial P}{\partial x}\right)_c. \quad (19)$$

It will also be assumed that in the limit of step shock loading a critical stress P^* must be exceeded to cause jetting from a cavity of depth x . In this approximation, the right-hand side of Equation (19) becomes

$$\left(\frac{\partial P}{\partial x}\right)_c \doteq \frac{P^*}{x}. \quad (20)$$

It is further assumed that the critical stress for jet formation is related to the yield strength as

$$P^* = Y/f. \quad (21)$$

where f is defined by the Y/P ratio where jetting is suppressed (Fig. 6).

As shown by the calculations in Figure 6b, f is about 0.2, and we will assume that it is an adjustable factor which can be evaluated from either experiment or numerical simulation. From the equations of motion, the applied stress gradient near the free surface is approximately related to free surface acceleration in Lagrangian coordinates as

$$\left(\frac{\partial P}{\partial x}\right)_a = \frac{1}{2\rho} \left(\frac{\partial u_{fs}}{\partial t}\right), \quad (22)$$

Figure 7. A wave of amplitude P with a finite shock width is shown incident on a cavity of depth x .

where ρ is the initial density. Equations (19)-(22) can be combined to provide a minimum free surface acceleration necessary to cause jetting from defects of depth x ,

$$\frac{\partial u_{fs}}{\partial t} > \frac{2Y}{\rho f x}. \quad (23)$$

Equation (23) can be evaluated for a given material, providing that the yield strength, cavity depth, density, and the factor f are known.

As mentioned, f can be evaluated from numerical simulation of jetting from cavities. It is also possible to evaluate it experimentally. The comparison achieved between experimental and calculational approaches will be illustrated to demonstrate the applicability of Equation (23) to jetting from surfaces with arbitrary defects. Recent experimental work¹⁵ has been reported in which the risetimes of shocks incident to aluminum surfaces were precisely controlled. For different surface accelerations, the amount of material ejected from the surface was then measured. The technique used to achieve continuous free surface acceleration is illustrated in Figure 8a and experimental results obtained on aluminum are shown in Figure 8b. These experiments indicated that a critical acceleration of about $2.5 \times 10^8 \text{ km/s}^2$ was necessary to induce mass ejection from aluminum surfaces containing natural defects. The dynamic yield strength of the aluminum (6061-T6) studied was about 0.25 GPa and the average defect depth was 3 μm (Table IV). Using these values in Equation (23) gives the factor f as approximately 0.24. As shown in Figure 6, this value is in general agreement with numerical results, which indicate that jetting should be completely suppressed for f values of about 0.2. This agreement and the assumptions stated earlier suggest that Equation (23) may be of general use for estimating the effects of shock risetime, although this possibility has not yet been verified for materials other than aluminum.

Figure 8. (a) Experimental technique for producing non-shock loading of a free surface. Experiments were conducted on 6061-T6 aluminum specimens for an impact stress of about 21 GPa. The ramp generator was a glass ceramic (Corning Pyroceram). (b) Ejecta mass as a function of wave risetime for the experiment depicted in (a). Time and mass resolutions are indicated by the dashed lines.

The acceleration of a surface can be influenced in primarily two ways. As illustrated by the technique shown in Figure 8a, input or boundary conditions can be used to control the shock wave risetime. In addition, dissipative response of a material may influence shock widths. For steady shock wave propagation, the viscous stress, ΔP , generated during shock compression of a hydrodynamic material is related to free surface acceleration approximately as¹⁶

$$\Delta P \doteq \frac{\eta}{2U} \left(\frac{\partial u_{fs}}{\partial t} \right) \quad (24)$$

where η is a viscous coefficient and U is the shock velocity. The importance of material viscosity on mass ejection can be made evident by combining Equations (23) and (24),

$$x > \frac{Y\eta}{\rho f U \Delta P} \quad (25)$$

Equation (25) indicates that the defect depth x necessary to cause jetting must exceed a critical value, which is influenced by the viscosity of the material. Since the viscous stress can be estimated for plane shock loading, the effects of viscosity on mass ejection can be determined from material properties alone.

The point to be emphasized by this discussion is that Equations (23) and (25) imply a minimum in defect depth which will cause mass ejection for given shock conditions. This observation has two important consequences. First, it suggests that there is a minimum surface roughness which should be sufficient to suppress ejection for given shock wave conditions. Thus, improving the finish of quite smooth surfaces may not necessarily decrease the amount of mass ejection. Second, it suggests a technique for suppressing ejecta, if it is not practical to improve surface finish. In these cases,

it may be possible to suppress ejecta by changing the input conditions so as to decrease the free surface acceleration. The experimental results achieved on ramp loading of aluminum surfaces illustrate this point.

The minimum defect size which can cause mass ejection has not been systematically investigated. One experiment conducted on a diamond-knife machined specimen of aluminum indicated that peak-to-valley depressions of $0.08\text{ }\mu\text{m}$ did not cause mass ejection (to within the experimental resolution of 0.5 ng/mm^2) for a shock pressure of 25 GPa (see Appendix A for a more detailed discussion of this result). However, this effect has not yet been verified in other materials. Therefore, further experimental work is necessary to determine the general applicability of Equation (25).

Application

Several investigations of shock-induced mass ejection have been reported which allow evaluation of the proposed model. In general, experiments have been performed for different materials, different surface conditions and different shock amplitudes. These various data can be combined using the results presented earlier which are expressible in the general form

$$m = V_E \quad (26)$$

where V_E is defined to be the effective defect volume per surface area. This factor contains information about the average cavity depth, angle and distribution. If the surface imperfections are accurately characterized, so that the effective defect volumes can be estimated, Equation (26) provides an estimate of the normalized ejecta mass. This estimate can then be compared with experimental measurements of total ejecta mass which are normalized by the initial material density.

Various experimental results have been summarized in Table IV, where the major surface imperfections have been identified in each case. For all of the results presented in the table, ranges in shock pressure were chosen so that neither dynamic yielding nor shock-induced melting should be important. The reported ejecta masses have been normalized by the initial density for each material. In some cases, a range of ejecta masses is given.

In most of the examples presented in the table, automated measurements of defect volume were used to reduce uncertainties in ejecta mass. In some cases, well-defined grooves were machined on surfaces of aluminum and gold. These experiments allow accurate determination of defect angle and depth and therefore of average defect volume. Furthermore, these data include reliable estimates of the deviation in cavity depth, so that the effects of distribution in depth can also be estimated.

For the other cases presented in the table, defect volumes could not be determined as precisely as for machine marks. For pits and scratches on polished surfaces, Quantimet¹⁷ analyses were used to estimate the areal density of defects. In all of these cases, pits were the major defects and scratches could be neglected. In order to estimate the pit volumes, we assumed that all pits were 90° conical depressions so that average depth could be estimated from average widths. Although this is definitely not the case, the results presented in Table II indicate that errors resulting from this approximation will not be large. Jetting factors of unity were also used in these cases, since this is essentially the average value of conical and cylindrical shaped cavities on a surface. Photographs of the surfaces studied also gave estimates of the distribution in defect width and therefore depth. Since $C(x)$ was estimated to be near 1.5 in most cases ($\sigma \approx 0.5 \bar{x}$), this value was used for all calculations.

TABLE IV
SURFACE ROUGHNESS PARAMETERS FOR SEVERAL MATERIALS

Material	Density Mg/m ³	Shock Pressure GPa	Ejecta Mass ^a μg/mm ²	Normalized Mass ^b m, mm	Type of Defects ^c	Average Defect Depth, μm	Areal Density of Defects, a _r	C(x) ^d	R(θ) ^e	C(θ)	Effective Defect Volume, V _E , mm
6061-T6 Al ⁶	2.70	25-36	0.03-0.14	1.1 - 5.2 x 10 ⁻⁵	pits ^f	3	0.011±0.002	1.5	1.0	1.0	1.7 x 10 ⁻⁵
6061-T6 Al ⁶	2.70	30	15-16	5.6 - 5.9 x 10 ⁻³	20° grooves	54±10	0.15	1.03	1.0	1.0	4.2 x 10 ⁻³
6061-T6 Al ⁶	2.70	30	16	5.9 x 10 ⁻³	30° grooves	48±13	0.20	1.07	0.8	0.8	4.1 x 10 ⁻³
6061-T6 Al ⁶	2.70	30	21-23	7.8 - 8.5 x 10 ⁻³	45° grooves	56±13	0.37	1.05	0.7	0.7	7.6 x 10 ⁻³
6061-T6 Al ⁶	2.70	30	26-31	9.6 - 11.5 x 10 ⁻³	85° grooves	48±18	0.70	1.14	0.7	0.7	1.3 x 10 ⁻²
Lead ⁷	11.3	9	0.1	8.9 x 10 ⁻⁶	pits ^f (vapor plated)	1.5	0.017±0.007	1.5	1.0	1.0	1.3 x 10 ⁻⁵
Lead ⁷	11.3	10-15	8-14	7.0 - 12.0 x 10 ⁻⁴	pits ^f (polished)	5	0.26±0.04	1.07	1.0	1.0	4.6 x 10 ⁻⁴
Gold ⁹	19.3	90	0.1-0.2	5.2 - 10.4 x 10 ⁻⁶	pits ^f	2	0.024±0.009	1.5	1.0	1.0	2.4 x 10 ⁻⁵
Copper-Gold ⁹	14.3	88	94-96	6.7 x 10 ⁻³	45° grooves	57±13	0.37	1.05	0.7	0.7	7.8 x 10 ⁻³
Copper-Tungsten ⁹	16.8	91	2.4-5.4	1.4 - 3.6 x 10 ⁻⁴	32 RMS (nominal)	2	1	1.0	0.7	0.7	7.0 x 10 ⁻⁴
Tungsten ¹⁸	19.2	25	300	1.6 x 10 ⁻²	pores ^g	13	0.40	1.5	1.0	1.0	5.2 x 10 ⁻³

^a In most experiments, ejecta mass was estimated with the thin foil technique described in References 5 and 6.

^b Normalized ejecta mass was determined by dividing measured ejecta mass by initial density.

^c The type of defects most predominant are identified and used to estimate defect density.

^d Where possible, the effects of distribution in defect depth were estimated using Equations (17) or (18).

^e The jetting factors were estimated without assuming a distribution in angle. If the apex angles of the defects were known, it was assumed that the total average angle was 90°.

^f Approximated as 90° conical cavities.

^g Approximated as hemispheres.

In one of the reported experiments, mass ejecta from a mechanical mixture of copper and tungsten was measured.¹⁸ The surface finish was quoted to be a 32 RMS finish, but was not actually measured with profile measurements. For these experiments, we estimated the machine mark depths from photomicrographs of the surface by assuming 90° linear depressions. The resulting depth was within 40% of the value expected from the quoted RMS value. In addition, the jetting factor for 90° was used. Because of the uncertainty in depth and angle we did not attempt to correct the estimated defect volume for distribution effects.

The last case shown in Table IV was a tungsten sample of approximately 27% porosity. The effective defect volume due to pores near the surface was found to be much larger than that due to other defects, such as scratches or machine marks, so that only the pore defects were considered. The effective volume for jetting from pores was estimated by approximating them as hemispheres and assuming that only those pores within one diameter of the surface contribute to mass ejection. The equation given in Table I was then used to determine the effective defect volume. Although the choice of one pore diameter as the effective defect depth is somewhat arbitrary, numerical calculations were performed which indicate that defects more than one depth length from the surface do not contribute substantially to mass ejection.

The experimental results are plotted in Figure 9 and compared to predictions of the model. The most exact correlation can be made between experimental results obtained for well-defined grooves on aluminum and copper-gold surfaces. For these cases, the differences between expected and measured ejecta masses are on the order of 30%. For the other materials, the determination of defect volume is more uncertain. Nevertheless, generally good agreement is obtained between measured and predicted values.

Figure 9. Predicted and measured normalized ejecta mass as a function of effective defect volume. Both normalized mass and defect volume are defined per unit area. Parameters for the experimental data are given in Table IV.

In nearly all cases, the differences between expected and measured ejecta masses are less than a factor of three in normalized mass for a given effective volume (the vertical bars given for some of the results represent ranges in the measured masses and are not error bars).

As mentioned above, the difference between measured and expected ejecta masses is at most about a factor of three. This is approximately the expected uncertainty for estimating ejecta mass. As indicated by Table III, errors in defect volume fall into four categories: the areal density of defects, their depth, and the effects of distribution in both depth and angle. The correction factor for angular deviations contains the dependence on geometry through the jetting factor. If video scanning of photomicrographs (Quantimet) is used to define the average areal defect density, $\bar{a}_r$, uncertainties in the average value are usually less than a factor of two.

For a random distribution of surface pits, it is necessary to estimate the average defect depth. Although optical diffraction techniques are becoming available for the purpose of studying individual defects,²⁰ defect depth can be estimated in most laboratories only from photomicrographs of the surface. If the apex angle of cavities is estimated to be 90° , this can be accomplished from an estimate of the average defect width. This approximation is expected to be good to within a factor of two in most cases.

The uncertainty in defect volume arising from distributions in defect size and angle can also be estimated from the earlier results. If the average values for angle and volume are used to define defect volume, the correction factors $C(x)$ and $C(\theta)$ allow an estimate of errors arising from distribution effects, providing the deviation from average values can be estimated. However, a more direct approach is to use the estimated fluctuations in depth and angle to obtain a better estimate of the effective defect

volume, as was done for the present results. When reasonable estimates of distribution effects are made, it is expected that resulting errors are less than a factor of two, since variations in $\bar{R}$ are usually small.

From these considerations, it should be possible to estimate defect volumes in general to within an expected RMS uncertainty of a factor of four. Although this degree of uncertainty appears to be large, it is not a severe restriction in many applications. Furthermore, it should be possible to reduce uncertainties in defect volume as better methods for characterizing arbitrary defects on a surface become available.

It should be pointed out that these arguments apply to the worst case of arbitrary defects on a surface. If the defects are reasonably uniform, such as machine cutting marks, it should be possible to use profile measurements to define average values and fluctuations sufficiently well that uncertainty in effective defect volume can be reduced to less than 50%. The results obtained on machined grooves illustrate this point, since the agreement between predicted and measured values is within 30%.

Limitations of the Model

There are several limitations to the technique which should be discussed. In many applications, determination of effective defect volume will be a limiting factor. However, through proper characterization of the sample surface, it should be possible to obtain reasonable estimates of defect volumes. The results presented here for jetting factors can then be used to estimate the effective defect volume.

Another possible limitation concerns additional mechanisms other than microjetting which may contribute to mass ejection. It has been assumed that microjetting from surface depressions is the only source of ejection.

Although the correlation shown in Figure 9 tends to support this conclusion, there is limited experimental evidence which suggests that breakup and ejection of material around foreign inclusions occurs in aluminum alloys.⁶ For this reason, the contribution of ejected particles to mass ejecta should be carefully considered in alloys. Furthermore, ejection of material by spallation from the free surface is not considered in the model. Such effects can result from non-uniform shock loading (e.g., from explosive loading).

Other sources of ejection include internal defects, such as grain boundaries or plastic deformation bands. However, experiments conducted on lead⁷ indicate that these sources are not important to mass ejection for shock pressures to 113 GPa, which is near that sufficient to induce surface boiling. This result has not been verified in other materials or in pressure ranges where boiling can occur. Thus, the possibility that internal defects can contribute to mass ejection should be kept in mind. In any case, the results presented earlier provide a lower limit to the ejected mass if other sources of ejection are present.

With regard to the assumptions used to develop the model, there are several possible limitations. One assumption was that ejecta mass is proportional to material density with the proportionality constant independent of material properties. This observation has not been verified in detail. However, the correlation obtained between ejecta masses from grooved surfaces of aluminum and copper-gold (Figure 5) lends support to the hypothesis. Furthermore, the good agreement between calculated and measured ejecta masses (Figure 9) for several different materials also supports the conclusion.

As discussed earlier, we have assumed that shock amplitude has no influence on mass ejection, except at low pressures where strength effects

are important. However, experimental evidence⁶ on lead surfaces with naturally occurring defects indicates that shock pressures sufficient to induce free surface melting cause an enhancement in the amount of material ejected by up to an order of magnitude. Because of this observation, the model should be used with caution in regions where melting occurs. However, since the influence of melting on mass ejection is not yet understood, it is appropriate to comment on this effect in terms of the previous development. Both yield strength and material viscosity will decrease when melting occurs, so that from Equation (25), smaller defects could contribute to mass ejection. In this case the main consequence of melting is to allow more sources of ejection. However, alternate explanations are also possible. For example, observations show that the enhancement occurs for ejecta velocities that are only a few percent greater than the free surface velocity. Thus, it can be speculated that the mass enhancement may simply be due to mass being emitted as a result of the melting itself and not due to mass enhancement resulting from jetting. Hopefully, it will be possible to resolve this question by performing mass ejection experiments near melt states on surfaces which are in some cases essentially defect free and in other cases prepared with uniform defect dimensions.

Another limitation of the model is that it does not predict maximum ejecta velocities. It is known that the shape of cavities strongly influences maximum jet velocities. From the experimental and numerical results presented earlier,^{6,9} the maximum jet velocity for 15° grooves in aluminum is found to be about three times greater than the free surface velocity (for a shock pressure of 30 GPa); whereas the maximum jet velocity for 90° grooves is about twice the free surface velocity. Calculations for 150° grooves show that the maximum velocity is only about 25% greater than free

surface velocity. Similarly, calculations for square grooves and cylindrical cavities indicate maximum jet velocities which are approximately 30% and 80% greater than free surface velocity, respectively. In principle, it should be possible to use statistical models along with known mass-velocity distributions to estimate the distribution of ejecta mass with velocity from surfaces containing arbitrary defects. Current methods for measuring defect properties are not sufficiently accurate to warrant this sophistication. However, it may be possible to use either measured maximum ejecta velocities to deduce the effective range of defect angles, or to predict approximate maximum ejecta velocities from knowledge of measured defect angles.

Finally, it should be noted that this model is based on the presumption of plane loading of surfaces containing defects. Multidimensional loading of surfaces or plane loading of oblique cavities may cause substantial variations in ejecta mass from the model discussed here. However, these limitations should not be significant if the radius of curvature of the shock is much larger than defect dimensions.

Although there are several restrictions and limitations associated with using the proposed model to estimate mass ejecta from shocked surfaces, it should be possible to make approximate estimates of ejecta mass for a given situation. The good correlation observed between predicted and measured ejecta masses in several materials tends to support this observation. In most cases, the greatest difficulty in using the model will probably be in making reliable estimates of defect volume on the surface.

III. CONCLUSION

A model has been presented for estimating the effects of surface roughness on mass ejection from shocked surfaces. Surface roughness is characterized by the total volume of defects on a surface. This parameter can be estimated from automated or visual measurements of surface profiles. The basic assumption in the technique is that mass ejection occurs primarily by microjetting from surface depressions, such as scratches, pits, or machine marks. Using this assumption and three simplifying observations about jetting processes, it is possible to obtain statistical relations between ejecta mass and defect volume in terms of a geometry-dependent parameter. This parameter, termed the jetting factor, gives the ratio of jet mass to cavity volume expected from a single cavity and can be evaluated from experimental measurements on surfaces containing well-defined defects or from numerical simulation of jetting from shaped cavities. Typically, the jetting factor is on the order of unity.

The model has been compared with experimental measurements of mass ejecta from six different materials containing a variety of surface defects. For total defect volumes ranging by over three orders of magnitude, it is found that measured and predicted ejecta masses agree to within a factor of three. This degree of variation is within expected uncertainties and provides strong support for the model. On the basis of this correlation, it is expected that ejecta masses can be estimated for arbitrary materials and surface conditions to at least within an order of magnitude.

Extensions to the model have also been discussed. The most significant factor which affects predicted ejecta masses is expected to be shock wave risetime. It is shown that finite accelerations of a surface result in a

minimum defect depth which can contribute to mass ejection. The minimum depth threshold can be estimated from material properties, such as yield strength, viscosity, shock velocity and density, along with a parameter which gives the minimum shock pressure sufficient to cause jetting. This limiting condition for mass ejection is important, both for estimating the surface finish necessary to suppress ejection and for controlling free surface acceleration so as to minimize ejection.

IV. ACKNOWLEDGEMENTS

We would like to acknowledge A. J. Toepfer, Org. 4242 and D. E. Grady, Org. 5532 for critically reviewing this work.

We also benefited from numerous conversations with J. F. Barnes, J. M. Walsh, and R. H. Warnes of Los Alamos Scientific Laboratory.

REFERENCES

1. J. K. Barnes, P. J. Blewett, R. G. McQueen, K. A. Meyer, and D. Venable, J. Appl. Phys., 45, 727 (1974).
2. K. A. Meyer and P. J. Blewett, Phys. Fluids, 15, 753 (1972).
3. J. R. Freeman, M. J. Clauser, and S. L. Thompson, Nuclear Fusion, 17, 223 (1977).
4. F. C. Perry and L. P. Mix, Appl. Phys. Lett., 24, 624 (1974).
5. J. R. Asay, F. C. Perry, and L. P. Mix, Appl. Phys. Lett. 29, 284 (1976).
6. J. R. Asay, "Material Ejection From Shock-Loaded Free Surfaces of Aluminum and Lead," Sandia Laboratories Report SAND 76-0542 (1976) (unpublished).
7. J. R. Asay, R. Mah, and R. W. Springer, to be published in J. Appl. Phys.
8. L. D. Bertholf, Bull. Amer. Phys. Soc., 23, 95 (1976).
9. J. R. Asay and L. D. Bertholf, "Mass Ejection From Material Interfaces Subjected to Impulse Loading," Sandia Laboratories Report SAND 78-0549, 4, (1978).
10. G. Birkhoff, D. P. MacDougall, E. M. Pugh, and G. Taylor, J. Appl. Phys., 19, 563 (1948).
11. E. M. Pugh, R. J. Eichelberger, and N. Rostoker, J. Appl. Phys., 23, 532 (1952).
12. R. J. Eichelberger, J. Appl. Phys., 26, 398 (1955).
13. L. D. Bertholf and J. R. Asay, to be published.

14. S. L. Thompson, "CSQ-A Two-Dimensional Hydrodynamics Program With Energy Flow and Material Strength," Sandia Laboratories Report SAND 74-0122 (1975).
15. J. R. Asay, "Effect of Shock Wave Risettime on Material Ejection From Aluminum Surfaces," Sandia Laboratories Report SAND 77-0731 (1977).
16. G. E. Duvall, "Shock Waves and Equations of State," in Dynamic Response of Materials to Intense Implusive Loading, Ed. by P. C. Chou and A. K. Hopkins, Air Force Materials Laboratory, Wright Patterson AFB, Ohio (1972).
17. We are indebted to R. Mah of Los Alamos Scientific Laboratory for suggesting this method and performing many of the analyses.
18. These samples were supplied by D. Venable, Los Alamos Scientific Laboratory.
19. Samples of porous tungsten were supplied by H. Anderson and J. E. Kennedy, Sandia Laboratories.
20. P. E. Klingsporn, "Measurement of Surface Defect Diameters, Widths, and Depths Using Reflected and Diffracted Light," (U) Bendix Corporation Report BDX-613-1876 Secret (1977) (unpublished).
21. L. C. Chhabildas and J. R. Asay, submitted to J. Appl. Phys. (1978).
22. R. G. McQueen, S. P. Marsh, J. W. Taylor, J. N. Fritz, and W. J. Carter, "The Equation of State of Solids From Shock Wave Studies," in High Velocity Impact Phenomena, Ed. by R. Kinslow, Academic Press, NY (1970).
23. L. R. Veaser and J. C. Solen, Phys. Rev. Lett. 40, 1391 (1978).
24. J. J. Gilman, ARPA MRC meeting, La Jolla, CA (1977) (unpublished).
25. S. K. Godunov, A. A. Deribas, and W. I. Mali, Combustion, Explosion and Shock Waves 11, 1 (1975).

APPENDIX A

ESTIMATION OF THE VISCOSITY OF ALUMINUM FROM JETTING EXPERIMENTS

As discussed earlier, shock risetime and defect size are crucial parameters which influence mass ejection from shocked surfaces. Thus, experiments on surfaces where mass ejection occurs can be used to establish approximate bounds on the risetime of the shock incident on the surface and therefore provide rough estimates of the effective viscosity of the material under shock compression.

It was previously shown that the minimum free surface acceleration sufficient to produce jetting from cavities should be approximately related to cavity depth x as

$$\frac{\partial u_{fs}}{\partial t} > \frac{2Y}{\rho f x} , \quad (A1)$$

where Y is the yield strength, ρ is density and f is the ratio of yield stress to the shock amplitude which suppresses jetting from wedged-shape cavities. As shown earlier, f is approximately 0.2 for aluminum. If the shock risetime and therefore the free surface acceleration is limited by rate-dependent material response, Equation (A1) can be expressed as¹⁶

$$\eta < \rho \frac{f U \Delta P x}{Y} \quad (A2)$$

where U is shock velocity and ΔP is the effective viscous stress obtained during shocking. Techniques have been previously discussed^{16,21} for estimating ΔP during shock loading. Y can be estimated from dynamic or static yield measurements²² and ρ and U are known from equation of state measurements²². Therefore, if experiments are conducted on surfaces

with different degrees of roughness (i.e., x) where mass ejection either occurs or does not occur, it is possible to estimate the viscosity of the material.

Experiments have been performed in the present work which provide approximate bounds on shock risetime and viscosity of aluminum under shock loading. As mentioned earlier, one experiment was conducted on a diamond-knife-machined surface of aluminum (6061-T6) where mass ejection was not observed. The peak-to-valley deviation (sawtooth cavities) for the sample was approximately $0.08\text{ }\mu\text{m}$. The shock pressure in the experiment was 25 GPa, the shock velocity was 7.03 km/s , the density of the sample was 2.70 g/cm^3 and the dynamic yield strength of the 6061-T6 aluminum alloy studied was 0.25 GPa. From Table I, we would expect approximately $0.11\text{ }\mu\text{g/mm}^2$ of material to be ejected from the surface. However, no material was ejected to within the mass resolution of the experiment (about 0.5 ng/mm^2). Thus, from Equation (A1) an upper limit of $1.2 \times 10^{10}\text{ km/s}^2$ is obtained for the free surface acceleration induced by the shock, since larger accelerations would have caused mass ejection. Since the final free surface velocity was about 2.54 km/s , this result indicates that the shock risetime is greater than approximately 0.2 ns. The maximum viscous stress for this experiment can be estimated from the maximum offset between the Rayleigh line and the Hugoniot²¹ and is found to be 3.6 GPa. Using this value in Equation (A2) provides a lower limit of 40 poise for the viscosity of aluminum during plane shock loading to 25 GPa.

We can also estimate upper limits for shock risetime and viscosity from experiments on aluminum where mass ejection was observed. As indicated in Table IV, ejection of material was obtained for 36 GPa shock loading of 6061-T6 aluminum specimens which contained surface defects with $3\text{ }\mu\text{m}$

average depth. In this case, Equation (A1) implies that the free surface acceleration exceeded $3.1 \times 10^8 \text{ km/s}^2$ and, therefore, that the shock risetime was less than 11 ns. These values indicate that the upper bound on the viscosity of aluminum is 2500 poise for a shock pressure of 36 GPa.

Thus, mass ejection experiments on aluminum over the stress range of 25-36 GPa imply that the shock risetime is between 0.2 ns and 11 ns and that the viscosity of shocked-load aluminum is between 40 and 2500 poise. Although these values cannot be taken too literally, they are compatible with recent theoretical and experimental investigations. Chhabildas and Asay²¹ found experimentally that the risetime of shock waves in aluminum was less than about 3 ns for shock pressures to 40 GPa. From these data, they inferred an upper limit of 1000 poise for the viscosity of aluminum. Similarly, Veerer²³ found that the risetime of laser-driven shock waves in aluminum was less than approximately 0.05 ns for shock pressures near 200 GPa. This result also implies a low viscosity. Finally, Gilman²⁴ has shown on theoretical grounds that risetimes should be on the order of 0.015 ns for very high shock pressures with an effective viscosity of approximately 5 poise. However, we note that these results are not in agreement with earlier Russian estimates of between 10^4 and 10^5 poise for the high pressure viscosity of aluminum. In this case, the shock risetime should be at least 42 ns at 36 GPa and mass ejection should not occur for cavity sizes less than 12 μm . Clearly, this disagrees with the present result and the other estimates of viscosity which have been recently published.

The general compatibility of the more recent studies of material viscosity with the present results is encouraging and lends support to our estimates of how shock risetime influences mass ejection. In view of this

agreement, it may be possible in general to obtain rough estimates of shock risetime and material viscosity from mass ejection experiments.

Distribution:

J. W. Hopson, MD-0
Los Alamos Scientific Laboratory
Mail Stop 680
Los Alamos, NM 87544

J. M. Christian, M-6
Los Alamos Scientific Laboratory
Mail Stop 970
Los Alamos, NM 87544

D. Venable, ADWPC
Los Alamos Scientific Laboratory
Mail Stop 682
Los Alamos, NM 87544

R. H. Warnes, M-4
Los Alamos Scientific Laboratory
Mail Stop 940
Los Alamos, NM 87544

W. F. Hemsing, WX-7
Los Alamos Scientific Laboratory
Mail Stop 950
Los Alamos, NM 87544

J. W. Conant, WX-7
Los Alamos Scientific Laboratory
Mail Stop 950
Los Alamos, NM 87544

J. M. Walsh, M-4
Los Alamos Scientific Laboratory
Mail Stop 682
Los Alamos, NM 87544

J. W. Taylor, TD-DO
Los Alamos Scientific Laboratory
Mail Stop 218
Los Alamos, NM 87544

B. W. Olinger, M-6
Los Alamos Scientific Laboratory
Mail Stop 970
Los Alamos, NM 87544

J. F. Barnes, T-4
Los Alamos Scientific Laboratory
Mail Stop 212
Los Alamos, NM 87544

G. N. White, TD-DO
Los Alamos Scientific Laboratory
Mail Stop 218
Los Alamos, NM 87544

R. G. Craig, M-3
Los Alamos Scientific Laboratory
Mail Stop 960
Los Alamos, NM 87544

R. L. Spaulding, WX-7
Los Alamos Scientific Laboratory
Mail Stop 950
Los Alamos, NM 87544

N. R. Borch, ADW-PM
Los Alamos Scientific Laboratory
Mail Stop 246
Los Alamos, NM 87544

J. N. Fritz, M-6
Los Alamos Scientific Laboratory
Mail Stop 970
Los Alamos, NM 87544

C. Mader, T-14
Los Alamos Scientific Laboratory
Mail Stop 212
Los Alamos, NM 87544

R. G. McQueen, M-6
Los Alamos Scientific Laboratory
Mail Stop 970
Los Alamos, NM 87544

J. N. Johnson, T-14
Los Alamos Scientific Laboratory
Mail Stop 212
Los Alamos, NM 87544

R. Mah, CMB-6
Los Alamos Scientific Laboratory
Mail Stop 770
Los Alamos, NM 87544

J. W. Shaver, M-6
Los Alamos Scientific Laboratory
Mail Stop 970
Los Alamos, NM 87544

R. W. Springer CMB-6
Los Alamos Scientific Laboratory
Mail Stop 770
Los Alamos, NM 87544

D. J. Sandstrom, CMB-6
Los Alamos Scientific Laboratory
Mail Stop 770
Los Alamos, NM 87544

Dr. R. R. Karpp, TD-5
Los Alamos Scientific Laboratory
Mail Stop 224
Los Alamos, NM 87544

T. R. Neal, M-2
Mail Stop 942
Los Alamos Scientific Laboratory
Los Alamos, NM 87544

R. Kirkpatrick, TD-2
Mail Stop 220
Los Alamos Scientific Laboratory
Los Alamos, NM 87544

K. A. Meyer, TD-9
Mail Stop 232
Los Alamos Scientific Laboratory
Los Alamos, NM 87544

D. S. Catlett, CMB-6
Los Alamos Scientific Laboratory
Mail Stop 770
Los Alamos, NM 87544

R. S. Thurston, WPO
Los Alamos Scientific Laboratory
Mail Stop 246
Los Alamos, NM 87544

M. L. Wilkins, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

Bill Nellis, L-504
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

L. L. Marino, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

J. W. Lyle, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

D. R. Goosman, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

A. C. Mitchell, L-504
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

G. T. Carpluk, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

M. Van Thiel, L-504
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

D. J. Steinberg, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

S. G. Cochran, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

N. L. Parker, L-24
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

W. H. Gust, L-504
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

L. B. Hord, L-504
Lawrence Livermore Laboratory
P. O. Box 808
Livermore, CA 94550

D. R. Curran, G-178
Stanford Research Institute
333 Ravenswood Avenue
Menlo Park, CA 94025

Dr. G. R. Fowles
Washington State University
Department of Physics
Pullman, WA 99163

Dr. J. Forbes
U. S. Naval Surface Weapons Center
White Oak
Silver Spring, MD 20910

L. R. Hettche
Naval Research Laboratory
4555 Overlook Avenue, SW
Washington, DC 20390

Dr. T. J. Ahrens
Seismological Laboratory 252-21
California Institute of Technology
Pasadena, CA 91125

D. Wiegand
Picatinny Arsenal
Dover, NJ

Dr. P. C. Chou
Drexel University
Philadelphia, PA 19104

N. H. Froula
K-Tech Corporation
P. O. Box 5489
Kirtland AFB
Albuquerque, NM 87115

W. J. Murri
Stanford Research Institute
333 Ravenswood Avenue
Menlo Park, CA 94025

H. E. Read
Systems, Science and Software, Inc.
P. O. Box 1620
La Jolla, CA 92037

R. M. Schmidt
P. O. Box 3999
The Boeing Company
Seattle, WA 98124

Dr. George Duvall
Washington State University
Department of Physics
Pullman, WA 99163

C. M. Huddleston
Naval Ordnance Laboratory
Silver Spring, MD 20910

Dr. S. M. Taylor, Jr.
USA Ballistic Research Laboratory
Aberdeen Proving Ground
Maryland 21005

D. G. Groves
National Academy of Sciences
National Materials Advisory Board
2101 Constitution Avenue, NW
Washington, DC 20418

Dr. D. P. Dandekar
Department of the Army
Army Materials and Mechanics
Research Center
Watertown, MS 02172

N. Abramson
Southwest Research Institute
8500 Culebra Road
San Antonio, TX 78228

Dr. R. E. Green, Jr.
Dept. of Mech. & Materials Science
Maryland Hall
The John Hopkins University
Baltimore, MD 21218

D. Keller
K-Tech Corporation
Kirtland AFB
Albuquerque, NM 87115

L. Lee
K-Tech Corporation
Kirtland AFB
Albuquerque, NM 87115

D. Paisley
Monsanto Research Corporation
Mound Laboratory
P. O. Box 32
Miamisburg, OH 45342

Dr. J. Carleone
Dyna East Corporation
227 Hernlock Road
Wynnewood, PA 19096

B. Amery
AWRE
Foulness Island
Southend-on-Sea
Essex, England

B. Lambourn
AWRE
Aldermaston
Berkshire, England

Nickolas J. Hoskins
AWRE
Aldermaston
Berkshire, England

W. W. Reese
AWRE
Aldermaston
Berkshire, England

R. Baragiola
Centro Atomico Bariloche (C.N.E.A.)
8400 S. C. de Bariloche - R. N.
Argentina

Commissariat A
L'energie Atomique
B. P. 27-94190 Villeneuve
St. Georges, France

Dr. P. E. Klinsporn
Bendix Corporation
Kansas City Division
P. O. Box 1159
Kansas City, MO 64141

Director, U. S. Army
Ballistic Research Laboratory
U. S. Armament Research & Development
Command
Aberdeen Proving Ground, MD 21005
Attn: Richard Vitalli
Andrew Dietrich
Fred Grace
John Zukas
W. L. Gillich
J. Majerus
W. Walters
G. Jonas
T. W. Wright

Commanding Officer
U. S. Army ARRADCOM
Dover, NJ 07801
Attn: Jim Beetle
Glenn Randers-Pehrson

AFATL/DLJW
Eglin Air Force Base, FL 32542
Attn: Col. J. J. Osborn
Maj. D. Matuska

Dr. J. J. Gilman, Director
Materials Research Center
Applied Chemical Corporation
Morristown, NJ 07960

Y. M. Gupta
Stanford Research Institute
333 Ravenswood Avenue
Menlo Park, CA 94025

R. Cooper
Aerospace Corporation
P. O. Box 92957
Los Angeles, CA 90009

W. M. Isbell
Effects Technology
Santa Barbara, CA 93102

1100 C. D. Broyles
2513 D. B. Hayes
2513 R. J. Burnett
2513 J. E. Kennedy
2513 D. E. Mitchell
2513 A. C. Schwartz
2513 P. H. Stanton
2513 S. Sheffield
4200 G. Yonas
4241 J. R. Freeman
4241 M. M. Widner
4241 L. Baker
4241 M. J. Clauser
4242 A. J. Toepfer
4242 J. Chang
4242 L. P. Mix
4242 F. C. Perry
4400 A. W. Snyder
4500 E. H. Beckner
5100 F. L. Vook
5110 R. L. Schwoebel
5130 G. A. Samara

5131	L. W. Davison	
5131	W. B. Benedick	
5131	R. A. Graham	
5150	J. E. Schirber	
5500	O. E. Jones	
5510	O. E. Jones (Actg)	
5520	T. B. Lane	
5530	W. Herrmann	
5530	D. E. Munson	
5531	L. D. Bertholf	
5531	W. T. Brown	
5531	D. L. Hicks	
5531	M. E. Kipp	
5531	M. M. Madsen	
5531	T. J. Burns	
5531	J. W. Swegle	
5532	B. M. Butcher	
5532	J. Lipkin	
5532	H. J. Sutherland	
5532	D. E. Grady	
5533	A. J. Chabai	
5533	W. R. Davey	
5533	F. R. Norwood	
5533	P. Yarrington	
5533	S. L. Thompson	
5533	J. M. McGlaun	
5534	W. Herrmann (Actg)	
5534	L. C. Chhabildas	
5534	C. H. Konrad	
5534	R. D. Hardy	
5534	J. R. Asay	(25)
5534	D. E. Cox	
5534	D. S. Drumheller	
5534	R. L. Kinchen	
5534	D. A. Benson	
8266	E. A. Aas	
3141	T. L. Werner	(5)
3151	W. L. Garner	(3)
3172-3	R. P. Campbell	
	DOE/TIC	(25)