NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

DOE/CE/26602-2

DEVELOPMENT OF
ADVANCED LOW-TEMPERATURE HEAT TRANSFER FLUIDS
FOR DISTRICT HEATING AND COOLING

Progress Report
for Period January 1, 1991- March 31, 1991

Drexel University
Philadelphia, Pennsylvania 19104

March 31, 1991

Prepared for

THE U.S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG01-90CE26602

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *EP*

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

THERMAL ANALYSIS OF n-ALKANE PHASE CHANGE MATERIAL MIXTURES

Young I. Cho, Eunsoo Choi, and Harold G. Lorsch
Mechanical Engineering and Mechanics Department
Drexel University
Chestnut and 32nd streets
Philadelphia, PA 19104, USA

ABSTRACT

Tests were performed to characterize the thermal behavior of a number of n-alkanes to be used as phase change materials (PCMs) in district cooling applications. Hexadecane and tetradecane were mixed in different fractions, and their thermal behavior was experimentally evaluated. Test results for melting temperature and fusion energy for laboratory grade hexadecane and tetradecane showed good agreement with data in the literature. However, values for commercial grade hexadecane were found to be considerably lower. In the range of temperatures of interest for district cooling, mixtures of tetradecane and hexadecane can be treated as homogeneous substances. However, their heats of fusion are slightly lower than those of the pure substances. Their melting temperatures are also lower by an amount that can be predicted.

Keywords

Phase change, melting point, freezing point, heat of fusion, melting point depression,
n-alkanes

INTRODUCTION

As a part of the development of advanced low-temperature heat transfer fluids to be used in district cooling systems, tests were performed to characterize the thermal behavior of a number of n-alkanes. The project concentrates on the potential of using phase-change-material (PCM) particles suspended in water at temperatures used in district cooling loops. These heat transfer fluids would have improved heat transfer properties and would reduce the volume of fluid that needs to be pumped. The proposed method is to add to the carrier fluid a quantity of a PCM whose phase-change (melting/freezing) temperature is between the send-out and the return temperature of conventional district cooling systems. The increased thermal capacity of the PCM/water mixture decreases the pumping volume required and therefore results in savings in pumping energy, which constitutes a large fraction of the total input energy of district cooling systems.

In order to optimize the saving in pumping energy that can be obtained from using a water/phase-change material (PCM) mixture as the primary heat transfer medium in a district cooling system, the phase change temperature of the PCM should be between 3°C and 10°C, depending on the design temperature of the primary cooling loop. Its latent heat should be as high as possible, it should form a slurry with water, it should exhibit little or no supercooling, be stable under repeated thermal cycling, be inexpensive, and preferably be chemically inert and non-toxic. Paraffin wax satisfies most of these conditions, and it has been previously used as thermal storage material (1 and 2). These waxes are well characterized. They consist of simple, long molecular chains of CH₂ units with a CH₃ unit at each end (Figure 1). The exact phase transition temperature depends on the length of the chain, increasing with increasing chain length. These substances are hydrophobic, and they have similar molecular structures.

The desirable phase change temperature for a district cooling system probably lies somewhere between the phase change temperatures of tetradecane (5.8°C) and pentadecane (9.9°C). Thus, a mixture of these two waxes may constitute a technically suitable PCM. On account of the high cost of pentadecane, mixtures of hexadecane (phase change temperature of 18.1°C) with tetradecane may constitute a more economical mixture. This is why the authors felt the need for a more detailed investigation of the latter mixtures.

DESCRIPTION AND CALIBRATION OF TEST APPARATUS

A duPont 1090 Differential Thermal Analyzer (DTA) was used in connection with a duPont 910 Differential Thermal Calorimeter (DSC) (3) in order to determine melting points and heats of fusion of potential PCM mixtures. Because the average mass of the samples was only 2 to 8 mg, an accurate scale was needed. A Mettler AE166 scale with an accuracy of 0.01 mg was therefore used in order to obtain results with three significant figures.

In order to determine the accuracy of the thermal analyzer system, nine samples with different amounts of distilled water were prepared and tested. The melting temperatures of these water samples are shown in Figure 2. Although the samples were of different sizes, the measured values of melting temperature were consistent; their standard deviation was 0.54°C. Figure 3 shows the measured fusion energies for the same samples. The solid horizontal line represents the fusion

Figure 1. Molecular structure of n-alkanes

Figure 2. Measured melting temperatures for water/ice samples of different size

Figure 3. Measured heats of fusion for water/ice samples of different size

Figure 4. Typical DSC output diagram

energy of water given in handbook data (2) which is equal to 333.67 J/g. The standard deviation of the measured values of fusion energy was 15.3 J/g, which is 4.6% of the mean value. In the range of 2 to 10 mg, there was no dependence on sample size for measured values of either melting temperature or heat of fusion.

In order to calibrate the DSC system for heat of fusion measurements, at least two sets of calibration data for two known substances are required. One set was represented by these measurements for the water-ice transition, the other set consisted of data for indium provided by the manufacturer. The cell constants for any specific melting temperature were then obtained by linear interpolation with respect to temperature between the cell constants for water and for indium.

The output of the DSC system is a curve that shows heat flow rate vs. temperature (Figure 4). Starting with the frozen substance, the sample is heated at a constant rate represented by the straight line in the left part of the diagram whose slope is the specific heat of the frozen sample. The first deviation from that line indicates a phase change. The phase change temperature is obtained by drawing a tangent to the curve beyond the phase change and intersecting it with the original linear portion of the curve, as illustrated in the figure. The heat of fusion is obtained by integrating the area between the actual curve and the original straight line. The DSC apparatus used for these measurements was programmed to print out these values automatically.

Figure 5. DSC output diagrams for different mixtures of laboratory grade hexadecane and tetradecane. Percentages indicate the weight fraction of tetradecane. The abscissa represents temperature, the ordinate represents heat flow rate.

TEST RESULTS

Laboratory grade (99% pure) hexadecane and tetradecane were used to prepare nineteen samples with various fractions of laboratory grade hexadecane and tetradecane. The test results shown in Figure 5 illustrate the effects of varying these fractions. Proceeding from Figure 5a to Figure 5e and from Figure 5j to Figure 5f, several trends become apparent. Pure hexadecane exhibits only a single phase change as shown in Figure 5a. In Figure 5b, a small amount of hexadecane has been added. Only a single phase change occurs, but the onset temperature, i.e., the melting point, is slightly lowered. When larger amounts of tetradecane are added (Figures 5c and 5d) the shape of the curves changes. This indicates that molecular rearrangement occurs at more than one temperature. This phenomenon of "phase transition" increases as the fraction of tetradecane increases, resulting in a lowering of the first (primary) melting point and its heat of fusion.

A similar effect is shown in Figures 5j through 5f. The pure hexadecane of Figure 5j has only a single melting point. When small amounts of hexadecane are added, both melting point and heat of fusion are lowered. In the range of 10% to 90% of either substance, multiple phase changes take place. In the other ranges, the primary phase change is dominant, and the mixture can be treated as a homogeneous solution.

The phase change temperatures for all tested samples are plotted in Figure 6. This includes all the data from Figure 5 plus additional data whose DSC output curves are not shown. The horizontal coordinate indicates the concentration of tetradecane by weight. Thus, 0% tetradecane (left margin) indicates pure hexadecane, and the right margin indicates pure tetradecane.

Figure 6. Measured melting temperatures for mixtures of laboratory grade hexadecane and tetradecane

The measured data for the pure substances show good agreement with published data (2). At low percentages of tetradecane additive, hexadecane displays a secondary phase change. In the range of 40% to 90%, a tertiary phase change occurs, but at a considerably lower temperature. For district cooling applications, these secondary and tertiary phase changes can be ignored, and the mixture can be treated as having only a single phase change. However, the fusion energy of that phase change is somewhat reduced below that of either of the pure substances as shown in Figure 7. Here, too, the measured data agree well with Reference 2 data, as shown in Table 1.

Table 1. Melting temperatures and the fusion energies of selected *n*-alkanes

Alkane	Melting Temperature (°C)			Heat of Fusion (J/g)		
	Ref.2	Measured lab.	Measured comm.	Ref.2	Measured lab.	Measured comm.
Tetradecane	5.8	5.4		227	234	
Pentadecane	9.9			206		
Hexadecane	18.1	17.2	12.6	236	224	191

* lab. : laboratory grade

* comm.: commercial grade

MELTING POINT DEPRESSION

In the ranges of 0% to 10% and 90% to 100%, the melting point depression theory (4) is applicable. These ranges are important because they cover a fairly wide spread of melting temperatures: from 10°C to 18°C and from 0°C to 5°C, respectively. The melting temperature depression is predictable in these ranges according to the following theory.

Freezing point depressions depend upon the concentrations of the solutions and the solvents employed. The freezing point depression of a solution can be obtained by multiplying the molal freezing point depression constant of the solvent, K_f , by the molality of the solution, m . Note that the molality is defined as the number of moles of solute dissolved in 1 kg of solvent. However, strictly speaking, the mole fraction of the solute rather than its molality should be used (4), but their numerical values are not very different. The freezing points of mixtures are always below those of their constituent pure substances. They are material properties, i.e., unique values for each material. They depend on the solvent only and are independent of the solute. This assumes that the solute does not form a solid solution with the solvent. If this occurs, the relationship is not valid.

The melting temperature depression constant, K_f , of hexadecane was calculated from the Figure 6 data by linear regression, and the result is shown in Figure 8. In this case hexadecane is the solvent and tetradecane the solute.

$$K_f = -8.74^\circ\text{C/mole} \quad (\text{for hexadecane})$$

The same method was used to calculate the melting temperature depression constant, K_f , of tetradecane, and the result is shown in Figure 9. In this case, tetradecane is the solvent and hexadecane the solute.

$$K_f = -15.33^\circ\text{C/mole} \quad (\text{for tetradecane})$$

Figure 7. Measured heats of fusion for mixtures of laboratory grade hexadecane and tetradeceane

Figure 8. Linear regression for the melting temperature depression constant of laboratory grade hexadecane (solvent) and laboratory grade tetradeceane (solute). $K_f = -8.74^\circ\text{C}/\text{mole}$

Figure 9. Linear regression for the melting temperature depression constant of laboratory grade tetradecane (solvent) and laboratory grade hexadecane (solute). $K_f = -15.33^\circ\text{C}/\text{mole}$

These melting point depression coefficients can be used to fill the gaps between the melting temperatures of tetradecane and hexadecane as well as the range below the melting temperature of tetradecane in Table 1. Of course, gaps between other combinations of n-alkanes can also be filled by this method.

COMMERCIAL GRADE MATERIAL

If the proposed improvement in heat transfer fluids is to be viable for district cooling applications, commercial grade PCMs must be used instead of laboratory grade chemicals because of the high cost of laboratory grade materials. Therefore, exploratory tests were also performed on commercial grade PCMs. Test results for melting temperatures and heats of fusion for various mixtures of a commercial grade hexadecane and a laboratory grade tetradecane are shown in Figures 10 and 11, accompanied by the laboratory grade data from Figures 6 and 7, respectively. The difference in melting temperatures between the laboratory grade and the commercial grade materials is considerable: almost 5°C . But the linear melting temperature depression is maintained in the ranges of 0 to 10% and 90% to 100%.

Figure 10. Measured melting temperatures for mixtures of laboratory grade tetradecane with laboratory grade and commercial grade hexadecane

Figure 11. Measured heats of fusion for mixtures of laboratory grade tetradecane with laboratory grade and commercial grade hexadecane

CONCLUSIONS

Experimental results for melting temperature and fusion energy for laboratory grade hexadecane and tetradecane show good agreement with handbook data. Mixtures of these two substances in the ranges of 10% to 90% by weight exhibit multiple phase changes.

In the ranges from 0 to 10% and from 90% to 100%, a single phase change is dominant. It is these ranges that are of interest for district cooling. The fusion energy of the mixtures in these ranges is slightly lower than that of the pure substances.

The melting temperature depression within these ranges is theoretically predictable. Using experimental data, the melting temperature depression constants of hexadecane and tetradecane were calculated to be $-8.74^{\circ}\text{C}/\text{mole}$ and $-15.33^{\circ}\text{C}/\text{mole}$, respectively.

Melting temperature and heat of fusion of commercial grade hexadecane were found to be considerably below values given in the literature and measured for laboratory grade materials.

ACKNOWLEDGEMENT

The authors acknowledge the financial support of the U.S. Department of Energy, The Office of Buildings and Community Systems under its Grant No. DE-FG01-90CE26602.

REFERENCES

1. Altman, M., Yeh, H., and Lorsch, H.G., Conservation and Better Utilization of Electric Power by Means of Thermal Energy Storage and Solar Heating, NTIS PB 210359, 1973.
2. Lane, G., ed., Solar Heat Storage: Latent Heat Materials, vol II, CRC Press, 1986.
3. "Instruction Manual, 910 Differential Scanning Calorimeter (DSC) System," duPont Company, 1980.
4. Mortimer, Charles E., Chemistry; A Conceptual Approach, D. Van Nostrand Company, 4th ed., 1979.

END

DATE
FILMED

6 / 29 / 93