DOE/PC/91304--T5

RECEIVED
USDOE/PETC

APR 01 1993

93 MAR 29 PM 1:34

LOW SEVERITY UPGRADING OF F-T WAXES WITH SOLID SUPERACIDS

DOE/PC/91304--T5

DE93 011453

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Quarterly Report

Principal Investigators

John W. Tierney
Irving Wender

Department of Chemical & Petroleum Engineering
University of Pittsburgh, Pittsburgh, PA 15261

Prepared for the Department of Energy
Grant No. DE-FG22-91PC91304
Report Period: December 1, 1992 through February 28, 1993

March 26, 1993

US/DOE Patent Clearance is not required prior to the publication of this document.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY

In the last quarter, a new class of solid superacids, including sulfated zirconium-hafnium oxides and ZrO_2/SO_4 modified by Mn and Fe, were synthesized and shown to be active for isomerization and hydrocracking of hexadecane ($\text{n-C}_{16}\text{H}_{34}$). The reaction was carried out in a tubing bomb under mild conditions: 2.5 MPa and 433 K. $\text{Pt}/\text{HfO}_2/\text{SO}_4$ catalyst exhibited a low activity for hydrocracking of n-C_{16} , but the addition of ZrO_2 to the sulfated hafnium improved its activity considerably. An 85 wt% conversion level was achieved when the molar ratio of ZrO_2 to HfO_2 reached 1:1, indicating the possibility of a synergistic effect between zirconium and hafnium. It has recently been reported that $\text{Mn,Fe}/\text{ZrO}_2/\text{SO}_4$ is about three orders of magnitude more active than ZrO_2/SO_4 for isomerizing $\text{n-butane}^{[1]}$. As a result, an 0.5% Mn 1.5% Fe/ ZrO_2/SO_4 catalyst was prepared according to a procedure given in a patent^[2]. It was found that, without Pt, the catalyst was inactive for hydrocracking of n-C_{16} , possibly by deactivation due to coking. It is interesting that a 68 wt% conversion level was achieved after incorporation of Pt along with a product distribution that was shifted towards longer chain paraffins.

ZrO_2/SO_4 has been reported to be a superacid with $\text{H}_0 < -16$ as measured by the Hammett indicator method. However, the acid strength of some ZrO_2/SO_4 based catalysts, such as the mentioned catalysts, could not be measured by using Hammett indicators because the catalysts are colored gray. We successfully modified an in situ FT-IR analytical system to characterize the acidity of these catalysts. We have applied the method using pyridine as adsorbate to demonstrate their acid strength. Preliminary results indicated a level of acidity of our catalysts which is consistent with their performance in hydrocracking of n-C_{16} . Evidence of H_2 dissociation on platinum to form protonic acid sites was detected. To better understand the

behavior of ZrO_2/SO_4 based catalysts in hydrocracking and to study the kinetics and mechanism of hydrocracking of n-alkanes, a fixed-bed reaction system was designed and construction is nearly complete. This system will be tested and applied to hydrocracking of long-chain paraffins.

WORK DONE AND CONCLUSIONS

Synthesis of Sulfated Zirconium-Hafnium Bimetallic Oxides

The preparation of sulfated zirconium-hafnium bimetallic oxides was done by dissolving different ratios of both salts (ZrOCl_2 , HfOCl_2) in distilled water. The aqueous solution was stirred for 60 minutes before hydrolyzing with aqueous NH_4OH at room temperature. The hydrolysis was allowed to continue until a pH of 9.5 was achieved. The precipitates were kept at this pH overnight. The suspension was then decanted and the precipitates were washed with distilled water until no chloride ion was detected in the filtrate. The precipitates were then dried in an oven at 383 K overnight. After drying, the solids were powdered to below 100 mesh. Sulfation of the hydroxides was carried out by stirring 15 ml of 1.0 N sulfuric acid per gram of hydroxide in a beaker for 60 minutes. After overnight drying, the sulfated hydroxides were ground to below 100 mesh. Impregnation of platinum was done by the incipient wetness method. On the basis of the amount of metal hydroxide used, 0.5 wt% of platinum was introduced to the solid surface, followed by drying at 383 K overnight. The materials were finally calcined at 873 K for three hours.

Five catalysts, $\text{Pt}/\text{ZrO}_2/\text{SO}_4$, $\text{Pt}/\text{HfO}_2/\text{SO}_4$, and $\text{Pt}/\text{ZrO}_2/\text{HfO}_2/\text{SO}_4$ with different Zr/Hf ratios were tested for their activities for n- C_{16} conversion in tubing bombs. The batch experiments were carried out at an initial H_2 pressure of 2.5 MPa, 433 K, and 60 minutes reaction time. Conversions versus $\text{ZrO}_2/\text{HfO}_2$ ratio are shown in Figure 1. The $\text{Pt}/\text{ZrO}_2/\text{SO}_4$

catalyst, as mentioned previously, gives a 74 wt% conversion for hydrocracking of n-C₁₆, whereas the Pt/HfO₂/SO₄ catalyst shows lower activity. However, the sulfated zirconium-hafnium oxide increases in activity with increase in the ZrO₂/HfO₂ ratio. An 80 wt% conversion level is achieved with a ZrO₂/HfO₂ ratio of one, exceeding the conversion of sulfated ZrO₂ alone by 6 wt% (reproducibility is ± 2 wt% in the tubing bomb). This suggests that a synergistic effect may exist between ZrO₂ and HfO₂. XRD analysis will be conducted to reveal the interaction between the two transition metal sulfated oxides. The changes of the ratio of ZrO₂/HfO₂ did not influence the hydrocracking selectivity since the product distribution showed a similar pattern for all catalysts (Figure 2).

Synthesis of Pt/0.5 wt% Mn, 1.5 wt% Fe/ZrO₂/SO₄ Catalyst

A sulfated zirconia based catalyst containing both Mn and Fe was prepared by the following co-precipitation method:

Fifty grams of zirconyl nitrate and suitable amounts of ferric nitrate and manganese nitrates were dissolved in distilled water to make 560 ml of solution. The aqueous solution was stirred for 60 minutes until the salts were dissolved completely. The hydrolysis was carried out by slowly adding 29.8 wt% NH₄OH with rapid stirring. The pH of the resulting reaction mixture was kept at 9.0. The reaction slurry was filtered and the filter cake washed with distilled water six times until the filtrate was nitrate free. The damp cake was applied to perforated plates, placed in a tray, and dried overnight in an oven at 383 K. After drying, the pellets were added slowly to a beaker containing 1.0 N sulfuric acid solution at room temperature. Fifteen ml of 1.0 N sulfuric acid per gram of pellet was used. The solution was decanted after the pellets were soaked for 60 minutes followed by drying overnight. The dry solids were ground to below 100 mesh before impregnation of platinum. On the basis of the amount of metal hydroxides used,

0.5 wt% of platinum was introduced to the solid surface by the incipient wetness method. After overnight drying, the solids were calcined at 550 °C for 4 hours. The catalyst prepared in this procedure was used for hydrocracking of n-C₁₆ with the same reaction procedure as previously discussed. The activity of Pt/ZrO₂/SO₄ based catalysts in the absence and in the presence of Mn and Fe are compared in Table 1.

Initially, the 0.5 wt% Mn, 1.5 % Fe/ZrO₂/SO₄ catalyst did not exhibit activity towards hydrocracking of n-C₁₆ which resembled that of ZrO₂/SO₄. There was evidence of catalyst deactivation caused by coking. As expected, addition of platinum improved the activity significantly. The results reported in Table 1 show that the Pt/Mn,Fe/ZrO₂/SO₄ catalyst (0.5 wt% Pt, 0.5 wt% Mn, and 1.5 wt% Fe) is active for isomerization and hydrocracking of n-C₁₆. At a 68.6 wt% total conversion level (10 wt% lower than that obtained with 0.5 wt% Pt/ZrO₂/SO₄), a 90.2% selectivity to isoparaffins is achieved. In contrast to 0.5 wt% Pt/ZrO₂/SO₄ catalyst, Pt/Mn,Fe/ZrO₂/SO₄ catalyst drives the product distribution towards longer chains; the C₁₀-C₁₃ fractions shows a dramatic increase compared with C₅-C₉ fractions. It may be that the presence of Mn and Fe weakens the acid strength but stabilizes the sulfate group bonded to ZrO₂, in keeping with our recent findings by FT-IR. The structural interaction between Mn/Fe and ZrO₂/SO₄ will be studied in future work.

In Situ FT-IR Analysis

During the last quarter, we successfully utilized an in-situ FT-IR analytical system. The apparatus is being used to characterize the nature and structure of acid sites on sulfated zirconium. The system is being operated not only under high vacuum (10⁻⁶ mm Hg), but also under pressures up to 200 psig depending on the strength of the CaF₂ windows. The maximum operating temperature of the IR cell is 400 °C. As shown in Figure 3, prior to the reaction, the

catalyst was pressed into a thin wafer (0.1 mm) to increase its transparency to the infrared beam. Figure 4 shows the system. Before analysis, the system and the cell were evacuated to a desired value. The amounts of reactant and adsorbates adsorbed were determined by measuring the differences in pressure before and after introducing adsorbates. The experimental data was recorded at 0.5 second/recording. Preliminary experiments indicate that the band at 1375 cm^{-1} , which is ascribed to S=O bond stretching vibration, can be an indication of the acid strength of sulfated zirconium catalysts. Importantly, the extent of the shift of this peak towards lower wave numbers after pyridine adsorption reveals the acid strength. The larger the shift, the higher the acid strength since this shift is caused by the strong interaction between pyridine and acid sites. The IR intensity of Bronsted acid sites was increased and Lewis acid sites weakened when Pt/ZrO₂/SO₄ catalyst was exposed to H₂, whereas such an effect was not observed with the ZrO₂/SO₄ catalyst. This clearly suggests that platinum is responsible for dissociating molecular hydrogen to generate protonic acid sites. In-situ Ft-IR analysis appears to provide a deep insight into the mechanism of the isomerization and hydrocracking of n-paraffins.

Continuous Flow Fixed Bed Reactor

To date, almost all studies have been conducted in a tubing bomb reactor. As reported previously, the catalyst pretreatment procedure is troublesome and time consuming. It is difficult to avoid the influence of moisture on catalytic activity. As a consequence, a continuous flow fixed-bed reaction system is being built in an attempt to pretreat our catalyst in situ and evacuate the moisture simultaneously. This system will help elucidate the mechanism and kinetics of isomerization and hydrocracking of long-chain paraffins. The reactor system is shown in Figure 5. The long-chain paraffins in liquid form will be pumped into the reactor by a micropump. The mass-flow meter controller is used to control the ratio of hydrogen to paraffins fed to the

reactor. Two check valves, with cracking pressure of 1.0 psig, are installed in both liquid and hydrogen feed lines to prevent the pump and mass flow controller from being blocked, since the pressure inside the reactor may build up during reaction. The reaction pressure will be controlled by a back pressure regulator installed at the outlet of the reactor. At different time intervals, reaction intermediates on the catalyst surface which may deactivate the catalyst will be washed out by a hydride donor, methylcyclopentane, stored in a saturator. The gas phase and liquid phase products will be separated through a visual cell and analyzed by GC and GC-MS.

FUTURE WORK

Various ZrO_2/SO_4 based catalysts promoted by small amounts of metals will be characterized by means of in-situ FT-IR. The influence of trace amounts of water on catalytic activity of the catalysts will be ascertained by introducing a known amount of water onto the catalyst surface through the vacuum system. The variation of Bronsted and Lewis acid sites on the catalyst will be monitored by FT-IR during isomerization of n-pentane. The FT-IR analysis will be reinforced by TPD techniques to provide more quantitative analysis of the superacidity of ZrO_2/SO_4 based catalysts. The continuous flow fixed-bed reactor will be tested and the kinetic results obtained will be related to some measurable property, such as acidity and acid strength, to help further understand the mechanism and kinetics of isomerization and hydrocracking of n-alkanes with solid superacids.

REFERENCES

1. C.H. Lin, C.Y. Hsu, **Chemical Communications**, **J. Chem. Soc.**, 20, 1479-1480, 1992.
2. Holletein et al., **US Patent** 4,918,041 (1990).

Table 1. Effect of Addition of Mn and Fe on Hydrocracking of n-C₁₆

Reaction Conditions		
Temperature, K	433	
Pressure, MPa	2.5	
Reaction time, min	60	
Product Distribution		
Catalysts :	0.5wt% Pt/ZrO ₂ /SO ₄	0.5wt% Pt/0.5wt% Mn, 1.5wt% Fe%/ZrO ₂ /SO ₄
Conversion, wt%	79.2	68.6
selectivity	83.6	90.2
C ₁ -C ₃	none	none
C ₄ -C ₉	51.2	25.6
C ₁₀ -C ₁₃	21.9	18.6
iso-C ₁₆	6.1	24.4

Figure 1. Activity of hydrocracking of n-C₁₆ with zirconium-hafnium oxides.

Figure 2. Selectivity of hydrocracking of $n\text{-C}_{16}$ with zirconium-hafnium oxides.

Figure 3. Cell employed for IR spectroscopy.

Figure 4. In situ FT-IR apparatus.

Figure 5. Scheme of fixed-bed reaction apparatus for hydrocracking of long-chain paraffins.

* BP : Back Pressure Regulator FC : Mass-Flow Controller
 PT : Pressure Transducer CV : Check Valve

END

**DATE
FILMED**

5 / 10 / 93