FOURTH ANNUAL REPORT

BEATRIX-II PROGRAM

JANUARY 1991 TO DECEMBER 1991

ANNEX-III TO IEA IMPLEMENTING AGREEMENT FOR
A PROGRAMME OF RESEARCH AND DEVELOPMENT ON
RADIATION DAMAGE IN FUSION MATERIALS

O. D. Slagle
G. W. Hollenberg

December 1992

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

MASTER

EXECUTIVE SUMMARY

The BEATRIX-II experiment is an International Energy Agency sponsored collaborative experiment between Japan, Canada, and the United States. The purpose of the experiment is to evaluate the performance of ceramic solid breeder materials in a fast neutron environment. The experiment is being conducted in the Fast Flux Test Facility (FFTF), located on the Hanford site near Richland, Washington, and operated by Westinghouse Hanford Company. The Pacific Northwest Laboratory, Richland, Washington, together with the Japan Atomic Energy Research Institute and Atomic Energy of Canada Limited (AECL) are responsible for conducting the experiment.

The work is divided into two phases: Phase I was irradiated from January 1990 until March 1991, in what is referred to as Cycle 11 of FFTF; Phase II was irradiated in Cycle 12, which began June 1991, and was terminated in March 1992.

Phase I

During 1990, the work focused on the irradiation testing of Phase I in FFTF Cycle 11. Phase I consisted of two Li_2O in situ tritium recovery canisters and a series of nonvented canisters. The experiment started on January 4, 1990, when the FFTF started its ascent to full power. During the period from January 1990 until March 1991, three subcycles were completed: 11-B.1 (85 effective full power days [EFPD]), 11-B.2 (134 EFPD) and 11-C (81 EFPD). The canisters were removed from the irradiation vehicle in April 1991, and were shipped to Argonne National Laboratory-West in May of 1991, for neutron radiography. The first series of radiographs were completed in June 1991, but selected radiographs were repeated during the October-December 1991 period.

The results of the BEATRIX-II, Phase I irradiation experiment provide an extensive data base on tritium recovery that gives insight into the in situ tritium release characteristics of Li_2O for lithium burnups to 5%. The particular implications of the results of the Phase I temperature-change canister are:

1. Decreasing the temperature directly affects the shape/size of the tritium recovery peaks observed during gas composition changes involving an increase in the hydrogen concentration and in several instances the lower temperatures gave delayed recovery peaks.
2. In general, reducing the amount of hydrogen in the helium sweep gas resulted in a larger change in tritium inventory during a given temperature transient and also resulted in a higher percentage of the recovered tritium being in the reduced form (HT).
3. The form of the tritium recovered (the amount of HT versus HTO) during a given temperature transient was found to change during the experiment. Specifically the amount of HTO decreased with increasing burnup and/or operating time. This could be due to burnup effects in the specimen, but alternatively, may result from changes in the tritium handling system, such as lower surface moisture.
4. Tritium recovery during startup and shutdown was strongly influenced by the composition of the sweep gas.

The Phase I temperature-gradient canister provided additional verification of the viability of Li_2O as a candidate for a fusion solid blanket. Results from the 300 EFPD of operation can be summarized as follows:

1. Throughout the 300 EFPD of irradiation, the temperature of the specimen was nearly constant or decreasing slowly. From the stability of the temperature, it is inferred that the microstructure and thermal properties of the specimen also remained stable and that the specimen remained physically intact.
2. The composition of the sweep gas was a critical parameter in the recovery of tritium from Li_2O . In general, decreasing/increasing the amount of hydrogen in the sweep gas appeared to decrease/increase the recovery rate of tritium. For sweep gases with smaller amounts of H_2 than the reference gas ($\text{He}-0.1\%\text{H}_2$), the apparent recovery rates are always less than the recovery rates in the reference gas for time periods of up to 10 days. However, it would appear that the effect of the sweep gas composition on recovery rate is almost entirely because of the effect of sweep gas composition on response of the ionization chambers. Ion chamber response appears to be dependent on the sweep gas composition with additions of 0.01, 0.1, and 1% hydrogen to the sweep gas, giving progressively higher response.

Radiographs of the Phase I vented canisters provide the first data on the physical condition of the ring and solid specimens. The ring specimen appears to have remained largely in place during irradiation, but an extensive amount of cracking can be seen. The temperature gradient specimen appears to be

intact, but the ends are domed upward, as if the hotter inner portion of the pellet stack swelled and increased in length.

Phase II

Phase II includes a temperature-change canister with a Li_2O specimen and a solid specimen of Li_2ZrO_3 spheres for performance studies. The fabrication of Phase II was completed in the first quarter of 1991, and irradiation started in FFTF Cycle 12-A.1. Cycle 12-A.1 (53 EFPD) started May 27, 1991, Cycle 12-A.2 (49 EFPD) started July 27, 1991, and Cycle 12-B.1 (50 EFPD) started November 21, 1991.

Preparation of the Phase II Li_2O ring specimen involved improved fabrication techniques resulting in a higher density, larger grain size material with a thinner wall for smaller temperature gradients. Li_2ZrO_3 was chosen as the alternative ternary breeder material and the material used was 1 to 1.5 mm diameter Li_2ZrO_3 spheres prepared by AECL Research.

An important design objective for Phase II was to achieve lower temperatures for the Phase II ring specimen than the Phase I Ring specimen. The design temperature for Phase II was 510°C for the inner thermocouple temperature and the final achieved temperature was 530°C . The original design calculations for the Phase II temperature gradient specimen predicted centerline temperatures in the range of 1160 to 1030°C . At startup, the measured centerline temperatures were 1104 and 1060°C for the top and bottom thermocouples, in good agreement with the design temperatures.

The Phase II test plan was similar to that used in Phase I. The tritium recovery behavior of the Phase II specimens from the start of the test in May 1991, to the end of 1991, was similar to Phase I. In general, the tritium recovery after temperature or gas composition changes occurred in a shorter time period for the Phase II specimens than for the Phase I specimens. These shorter response times may be characteristic of the higher density, larger grains sized Li_2O and of the Li_2ZrO_3 spherebed.

ACRONYMS

AECL	Atomic Energy Canada Limited
ANL-W	Argonne National Laboratory-West
CEC	ceramic electrolysis cell
DOT	Department of Transportation
EFPD	effective full-power day(s)
FFTF	Fast Flux Test Facility
I&C	instrument and control
IEA	International Energy Agency
JAERI	Japan Atomic Energy Research Institute
MCDM	Modelers and Code Developers Meeting
MOTA	Materials Open Test Assembly
PNL	Pacific Northwest Laboratory
SPND	self-powered neutron detector
TD	theoretical density
TSTA	Tritium System Test Assembly
WHC	Westinghouse Hanford Company

CONTENTS

EXECUTIVE SUMMARY	iii
ACRONYMS	vii
1.0 INTRODUCTION	1.1
1.1 OBJECTIVE	1.1
1.2 SCOPE	1.1
1.2.1 Phase I: Scope	1.2
1.2.2 Phase II: Scope	1.2
2.0 BACKGROUND	2.1
2.1 REVISED RESPONSIBILITIES	2.3
3.0 COSTS AND SCHEDULES	3.1
3.1 PHASE I FUNDING	3.1
3.2 PHASE II FUNDING	3.3
3.3 POSTIRRADIATION EXAMINATION OF PHASE I AND PHASE II	3.4
3.4 FUNDING STATUS	3.5
4.0 TECHNICAL STATUS	4.1
4.1 BEATRIX-II, PHASE I	4.2
4.1.1 Phase I: Temperature-Change Canister	4.4
4.1.2 Phase I: Temperature-Gradient Canister	4.12
4.1.3 Phase I: PIE - Radiographs	4.26
4.2 BEATRIX-II, PHASE II FABRICATION	4.28
4.2.1 Temperature-Change Canister	4.30
4.2.2 Temperature-Gradient Canister	4.31
4.3 BEATRIX-II, PHASE II IRRADIATION	4.36
4.3.1 Phase II Temperature-Change Canister	4.36

4.3.2	Phase II Temperature-Gradient Canister Operation . . .	4.45
4.4	DATA TRANSFER TO THE MODELERS AND CODE DEVELOPERS	4.49
4.4.1	Calibration of BEATRIX-II Ion Chambers in 0.1% H ₂ Purge Gas	4.49
4.4.2	Ion Chamber Background	4.50
4.4.3	Gas Composition Effects	4.51
4.4.4	Data Selection for BEATRIX-II MCDM	4.53
4.4.5	Data Sets Transferred	4.54
4.4.6	Data Transfer Participants	4.62
4.5	FINAL DATA CORRECTION/COMPILATION	4.62
4.6	TRITIUM PERMEATION EXPERIMENT	4.63
4.7	TRITIUM SYSTEMS TEST ASSEMBLY INTERFACE	4.64
5.0	REFERENCES	5.1
APPENDIX A	- EXPERIMENTER'S LOG FOR BEATRIX-II, PHASE I IN FFTF CYCLE 11-C	A.1
APPENDIX B	- EXPERIMENTER'S LOG FOR BEATRIX-II, PHASE II IN FFTF CYCLES 12-A AND 12-B IN CY 1991	B.1
APPENDIX C	- EXPERIMENTER'S LOG FOR BEATRIX-II, PHASE I IN FFTF CYCLE 11-C	C.1

FIGURES

4.1	Tritium Concentration for the Phase I Temperature-Change Canister During Temperature Changes from 550 to 650°C in Sweep Gas Compositions of He-0.1% H_2 , He-0.01% H_2 , and He	4.5
4.2	Tritium Concentration for the Phase I Temperature-Change Canister During Sweep Gas Composition Changes of He-0.1% H_2 , 2 Days in He-0.01% H_2 , 4 Days in He, He-0.1% H_2 at 550 and 650°C	4.7
4.3	Tritium Concentration for the Phase I Temperature-Change Canister During Temperature Changes from 550 to 650°C After Irradiation Periods of 80, 215 and 290 EFPD	4.8
4.4	Recovered Tritium Concentration and Temperature of the Phase I Temperature-Control Canister During a Reactor Shutdown in a Helium Sweep Gas	4.9
4.5	Center Temperatures for the Temperature-Gradient Capsule During Phase I Irradiation	4.14
4.6	Tritium Recovery Concentrations During Sweep Gas Composition Changes in the Phase I Temperature-Gradient Specimen for Tests #13 and #14	4.17
4.7	Tritium Recovery Concentrations and Sweep Gas Moisture for a Change from He-0.1% H_2 to He-1% H_2 Sweep Gas Through the Phase I Temperature-Gradient Specimen	4.19
4.8	Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in a Helium Sweep Gas	4.22
4.9	Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in a He-0.01% H_2 Sweep Gas	4.24
4.10	Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in Helium and 6 Days in He-0.01% H_2 Sweep Gas	4.25
4.11	Neutron Radiograph of Phase I Temperature-Change Canister After Irradiation	4.27
4.12	Neutron Radiograph of Phase I Temperature-Gradient Canister After Irradiation	4.29
4.13	Phase II Temperature-Change Capsule with the Loaded Specimen, the "Backup" Specimen, and the Inner Perforated Tube before Final Assembly	4.32

4.14	X-Ray Radiograph of the Phase II Temperature-Change Canister As-Fabricated	4.33
4.15	Li_2ZrO_3 Spheres As-Loaded in the Phase II Temperature-Gradient Canister	4.35
4.16	X-Ray Radiograph of the Phase II Temperature-Gradient Canister As-Fabricated	4.37
4.17	Tritium Recovery Following Temperature Transients from 535 to 645°C for the Phase II Temperature-Change Canister at 7, 51 and 61 EFPD	4.39
4.18	Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645°C in a Sweep Gas of He-0.1% H_2	4.41
4.19	Comparison of the Tritium Recovery Peaks Associated with a Temperature Change from 550 to 650 of the Phase I Peak at 295 EFPD and the Phase II Peak at 7 EFPD	4.42
4.20	Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645°C in a Sweep Gas of He-0.01% H_2	4.43
4.21	Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645°C in a Sweep Gas of He	4.44
4.22	Centerline Temperatures for the Operation of the Phase II Temperature-Gradient Canister During FFTF Cycles 12-A.1 and 12-A.2	4.46
4.23	Recovered Tritium Concentrations for the Phase II Temperature-Gradient Canister During 2-, 4- and 8-Day Tests Using He Sweep Gas	4.48
4.24	Recovered Tritium Concentration and Inner Thermocouple Temperature for Data Set #1 of the Phase I Temperature-Gradient Canister Transferred at the MCDM	4.55
4.25	Temperature Distribution Across the Thickness of the Phase I Ring Specimen Over the Range of Inner Temperatures	4.57
4.26	Recovered Tritium Concentrations at 650 and 550°C for Sweep Gas Composition Change Series of He-0.1% H_2 , 8 Days in He, 3 Days in He-0.01% H_2 , then Finally Back to He-0.1% H_2 for the Phase I Temperature-Change Canister	4.58

4.27	Tritium Recovery Curves for Temperature Transients of 650-550-650°C Carried Out During Cycle 11-B.1, Cycle 11-B.2, and Cycle 11-C for the Phase I Temperature-Change Canister	4.59
4.28	Recovered Tritium Concentration and Inner Thermocouple Temperature for Data Set #4 Through a Reactor Outage for the Phase I Temperature-Change Canister	4.60
4.29	Recovered Tritium Concentration and Relative Neutron Intensity for Data Set #4 Through a Reactor Outage	4.61

TABLES

2.1	Chronology of Events During 1991	2.2
2.2	Organizational Structure of BEATRIX-II	2.4
3.1	BEATRIX-II, Phase I Funding Schedule	3.2
3.2	BEATRIX-II, Phase I Actual and Projected Expenditures	3.2
3.3	BEATRIX-II, Phase II Funding Schedule for Funds Received and Projected	3.3
3.4	BEATRIX-II, Phase II Actual and Projected Expenditures	3.4
3.5	Projected Funding Schedule for BEATRIX-II Postirradiation Examination	3.5
3.6	Projected Financial Status for BEATRIX-II, Phase I and II as of January 1, 1992	3.5
4.1	Materials and Environmental Conditions for BEATRIX-II	4.3
4.2	Experimental Test Plan for the Solid Li_2O Specimen During FFTF Cycle 11-C	4.13
4.3	Effect of Sweep Gas Composition on Ion Chamber Background	4.20
4.4	Description of BEATRIX-II, Phase II Ring Specimen/Canister	4.31
4.5	Predicted Thermal and Neutronic Performance of the BEATRIX-II Li_2ZrO_3 Sphere Bed Canister	4.34
4.6	BEATRIX-II Ion Chamber Calibration - Phase I	4.50
4.7	Data Sets Transferred to MCDM Participants	4.54

1.0 INTRODUCTION

The BEATRIX-II experiment is an International Energy Agency (IEA) sponsored collaborative experiment between Japan, Canada, and the United States. This is an in situ tritium recovery experiment conducted to evaluate the performance of ceramic solid breeder materials in a fast neutron environment to high burnup levels. The experiment was carried out in the Fast Flux Test Facility (FFTF), located on the Hanford site near Richland, Washington, and was operated by Westinghouse Hanford Company (WHC). Pacific Northwest Laboratory (PNL),^(a) Richland, Washington, together with the Japan Atomic Energy Research Institute (JAERI) and Atomic Energy Canada Limited (AECL) Research are responsible for conducting the experiment.

1.1 OBJECTIVE

The objective of the BEATRIX-II experiment is to design, conduct, and evaluate the in situ recovery of tritium from solid breeder materials during neutron irradiation in the FFTF. During the experiment, the performance of candidate solid breeder materials is continuously monitored with respect to temperature stability and tritium release. The Phase I experiment was irradiated to lithium burnups of 5% while the goal for Phase II was to irradiate to burnups as high as 8%.

1.2 SCOPE

The BEATRIX-II experiment, as described in ANNEX-III, is divided into Phase I and Phase II. Phase I irradiation activities were carried out in Cycle 11 of FFTF between January 4, 1990 and March 20, 1991. Phase II irradiations were carried out beginning in Cycle 12 of the FFTF (May 27, 1991). Goal burnup is expected to be achieved in 300 EFPD, which should be reached in October 1992. However, operation after March 1992, is dependent on approval by US/DOE for the continued operation of FFTF. If the test is terminated at the end of March 1992, then it is expected that 200 EFPD will

(a) Pacific Northwest Laboratory is operated for the U.S. Department of Energy by Battelle Memorial Institute under Contract DE-AC06-76RLO 1830.

have been achieved. Postirradiation examinations of Phase I and II will be performed following the irradiation periods.

1.2.1 Phase I: Scope

The scope of Phase I of the BEATRIX-II experiment included the irradiation of two Li_2O in situ tritium recovery canisters. One specimen is a ring specimen having a nearly uniform temperature profile, and it is capable of temperature changes that provide data on the effect of temperature transients on tritium release. The other specimen, a solid column of Li_2O , provides performance data on Li_2O under a thermal gradient. Nonvented capsules are used to characterize radiation damage in single crystals, the effect of radiation on thermal conductivity, and the compatibility of beryllium with solid breeder materials.

1.2.2 Phase II: Scope

The scope of Phase II of the experiment is similar to Phase I because a temperature-change canister and a temperature-gradient canister are being irradiated. These two in situ tritium recovery canisters are, respectively, a Li_2O ring specimen and a solid Li_2ZrO_3 specimen composed of spheres with diameters in the range of 1 to 1.5 mm. In order to increase the total burnup of the specimens over that achieved in Phase I, the ^6Li enrichment was increased from 61 to 95 at% for both specimens, and the canister containing the Li_2ZrO_3 sphere specimen was positioned in a higher fluence position. Nonvented capsules included barrier-coated stainless steel specimens for tritium permeation studies at high temperatures and the inclusion of some of the beryllium-solid breeder material compatibility capsules irradiated to higher exposures.

2.0 BACKGROUND

BEATRIX-II received the technical approval to proceed in January 1988, with the approval of ANNEX-III. In March 1988, the final design review of Phase I was held and the fabrication and installation phase of the program was initiated. Specimens for the vented and nonvented canisters were fabricated in 1988, and the final canister assembly and installation on the materials open test assembly (MOTA) was completed in 1989. Fabrication of the tritium measurement system and MOTA Instrumentation and Control (I&C) system started early in 1988, and the first components were moved to FFTF in late 1988. During the first part of 1989, additional components were installed in FFTF and installation and checkout were completed in August 1989. A final checkout test using tritium was carried out in October 1989, and the MOTA assembly containing BEATRIX-II was inserted into FFTF in November 1989. The experiment started on January 4, 1990, when the FFTF started its ascent to full power. During the period from January 1991 until December 1991, two subcycles were completed: 11-B.1 (85 EFPD) and 11-B.2 (134 EFPD).

The scope and funding for Phase II was initially approved by the IEA Executive Committee at its December 1989, meeting in Tokyo, and final approval of the amendments to the ANNEX III of the Implementation Agreement was granted at the September 1990, meeting in Garching, Germany. Phase II includes a temperature-change canister with an Li_2O specimen and a solid specimen of Li_2ZrO_3 spheres for performance studies.

This annual report covers the period from January 1, 1991 to December 31, 1991. Table 2.1 lists the chronology of events during this period.

The primary focus of the work this year was the completion of the Phase I irradiation in FFTF Cycle 11, the fabrication of Phase II, and the start of Phase II irradiation in FFTF Cycle 12. Cycle 11-C of FFTF started late in December of 1990, and continued until March of 1991, for 81 EFPD. The Phase I canisters were removed from the irradiation vehicle in April 1991, and shipped to Argonne National Laboratory-West (ANL-W) in May of 1991, for neutron radiography. The first series of radiographs were completed in June 1991, but selected radiographs were repeated during the October to December

TABLE 2.1. Chronology of Events During 1991

Date	Event/Location	Participants	Impact
12/21/90	Start of Cycle 11-C	WHC	
3/21/91	End of Cycle 11-C	WHC	
3/22/91	B-II Working Group, Washington, DC	B-II Working Group	Establish Basis for Data Transfer
4/6/91	Disassembly of MOTA-2A	WHC	Removal of Phase I Vented Canisters
5/27/91	Start of Phase I Irradiation, Cycle 12-A.1	WHC	
5/30/91 to 6/1/91	FFTF Symposium Pasco, Washington	K Noda	Status Review of B-II in FFTF
7/27/91	End of Cycle 12-A.1 (53 EFPD)	WHC	
7/30/91	Start of Cycle 12-A.2	WHC	
9/21/91	End of Cycle 12-A.2	WHC	
9/26-27/91	B-II Experimenters Meeting, AECL, Ontario	B-II Experimenters	Establish Data Analysis Proce- dures and Data Sets for Transfer
10/9-10/91	BEATRIX-II Status Report: Tokyo, Japan	GW Hollenberg T Kurasawa K Noda	
11/15/91	B-II Working Group, Clearwater, Florida		
11/16/91	Modeler and Code Developers Meeting	Participants Representatives	B-II, Phase I Data Transfer
11/21/91	Start of Cycle 12-B.1	WHC	

1991, period. The fabrication of Phase II was completed in the first quarter of 1991, and irradiation started in FFTF Cycle 12-A.1. Cycle 12-A.1 (53 EFPD) started May 27, 1991, Cycle 12-A.2 (49 EFPD) started July 30, 1991, and Cycle 12-B.1 (50 EFPD) started November 21, 1991.

The BEATRIX-II Working Group held two meetings, one on March 22, 1991, in Washington, D.C., and one on November 15, 1991, in Clearwater, Florida. At

the March 22, 1991, meeting the basis was established for transferring the BEATRIX-II data to individuals who would use the data in developing mechanistic models describing the irradiation behavior of solid breeder materials and/or the development of computer codes for describing the irradiation behavior. The individuals involved in this data transfer were to be selected by the BEATRIX-II participants. At the BEATRIX-II experimenter's meeting held on September 26 and 27, 1991, at AECL Research, Chalk River, Ontario, five different data sets were selected and then transferred at the Modelers and Code Developers Meeting (MCDM) held November 17, 1991, in Clearwater, Florida.

K. Noda participated in a symposium sponsored by WHC to discuss the future uses of FFTF on May 30 to June 1, 1991. He presented a review of BEATRIX-II as an example of the application of FFTF to the development of fusion solid breeder materials. G. W. Hollenberg, T. Kurasawa and K. Noda participated in a review of BEATRIX-II at JAERI Headquarters in Tokyo on October 9 and 10, 1991.

2.1 REVISED RESPONSIBILITIES

The basic organization of the BEATRIX-II experiment was similar to that described in the 1990 Annual Report (Slagle and Hollenberg 1991) with some minor revisions. An organization diagram is shown in Table 2.2. The IEA Executive committee, which had the responsibility for approval and signing of ANNEX-III, is responsible for any changes or additions. The BEATRIX-II Working Group is a technical steering committee for the preparation and supervision of budgets, schedules, and scientific activities. During the past year, IJ Hastings served as the chairman of the BEATRIX-II Working Group. The responsibilities of operating the experiment evolved over the past year as the experiment's scope expanded from a fabrication/installation/operational mode to include the post-irradiation examination conducted during BEATRIX-II, Phase I.

TABLE 2.2. Organizational Structure of BEATRIX-II

3.0 COSTS AND SCHEDULES

Funding for BEATRIX-II is divided into Phase I and Phase II. Phase I was the first test series carried out in Cycle 11 of the FFTF/MOTA; Phase II is the second test series carried out in Cycle 12. Phase I and Phase II involve completely separate irradiation canisters.

The initial projected start of Cycle 11 MOTA given in the 1988 Annual Report (Hollenberg 1989) was April 29, 1989. However, as described in the 1989 Annual Report (Slagle and Hollenberg 1990b) a series of problems encountered during installation and increased administrative controls resulted in the start of the experiment being delayed beyond that date. BEATRIX-II, Phase I started with the start of Cycle 11B, which occurred on January 4, 1990. The 1990 Annual Report (Slagle and Hollenberg 1991) describes the activities carried out during the first year of irradiation. Completion of the irradiation of Phase I in the FFTF MOTA-2A assembly occurred in March 1991. The design of Phase II was established at a design review in September 1990, and fabrication of Phase II was initiated at this point. The fabrication and installation of the BEATRIX-II, Phase II canisters on the MOTA-2B assembly was completed in March 1991. MOTA-2B was installed in the FFTF and Phase II irradiation was initiated in May 1992.

3.1 PHASE I FUNDING

Phase I funding for BEATRIX-II was documented by ANNEX-III. The Phase I funding schedule is listed in Table 3.1. The total actual dollars received are listed together with the equivalent 1988 \$K, which are equal to the funds specified in ANNEX-III.

Table 3.2 is a listing of actual and projected costs of Phase I at the end of FY 1991 (October 1, 1991). The "Cost Recovery Funds" amounting to a total of \$632K are associated with recovering costs associated with BEATRIX-II, Phase II MOTA canisters that are not used in Cycle 12. These cost recovery funds were described in the 1990 Annual Report (Slagle and Hollenberg 1991). There are slight changes in the previously projected expenditures and

TABLE 3.1. BEATRIX-II, Phase I Funding Schedule (U.S. Dollars, \$K)

Participant	Initial	1988	1989	1990	Actual Total	Equivalent 1988 \$K (ANNEX III)
Canada		60	60		120	117
Japan	400	443	428		1271	1252
U.S.	180	497	397	210	1284	1251
TOTAL					2675	2620
Inflation Factor ^(a)			1.036	1.036		

(a) The inflation factor is used to convert actual 1989 and 1990 \$K to 1988 \$K.

TABLE 3.2. BEATRIX-II, Phase I Actual and Projected Expenditures (U.S. Dollars, \$K)

	Actual Expenditures			Projected Expenditures	Total
	FY 1989	FY 1990	FY 1991	FY 1992	
Design	250				250
Fabrication/Assembly	240	10			650
MOTA 1-C System	137				137
Sweep Purge Gas System	1278	69			1347
MOTA Irradiation:					
Operation	0	170	140		310
FFTF Charges	134	250	285		669
Disassembly	0	0	70		70
Engineering Support	92	39	0		131
Cost Recovery	-120	0	-240	-272	-632
TOTAL	2411	538	255	-272	2932

cost recovery for FY 1991, but the total projected cost of Phase I of \$2932K remains the same as projected in the 1990 Annual Report (Slagle and Hollenberg 1991).

3.2 PHASE II FUNDING

The scope and funding for Phase II and the funding for postirradiation examination was initially presented to the IEA Executive Committee at the December 1989, meeting in Tokyo. Final approval was obtained at the IEA Executive Committee Meeting in Karlsruhe, Germany, in September 1990. ANNEX-III was then revised and approved. The funding schedule for Phase II is shown in Table 3.3. The total actual funds are listed together with the equivalent 1989 \$K, which are consistent with those given in ANNEX-III. The actual and projected costs of Phase II at the end of FY 1991, are given in Table 3.4. The distribution of the funds is different than reported in the 1990 Annual Report (Slagle and Hollenberg 1991) but the total funding is the same.

TABLE 3.3. BEATRIX-II, Phase II Funding Schedule for Funds Received and Projected (U.S. Dollars, \$K)

Participant	1989	1990	1991	1992	Actual Total	Equivalent 1989 \$K (ANNEX-III)
Canada		60 ^(a)	60 ^(a)		120	120
Japan	14	515	495		1024	968
U.S.		390	553	(93)	1036	969
TOTAL					2180	2057
Inflation Factor		1.036	1.045	1.045		

(a) Non-inflating.

TABLE 3.4. BEATRIX-II, Phase II Actual and Projected Expenditures
(U.S. Dollars, \$K)

	Actual Expenditures		Projected Expenditures	Total
	FY-1990	FY-1991	FY-1992	
Design	60			60
Fabrication/Assembly	330	420		750
Tritium Handling System		13	41	54
Permeation Experiment		21	0	21
MOTA Irradiation Operation		129	370	499
FFTF Charges		83	525	608
Disassembly			74	74
Engineering Support		41	58	99
TOTAL	390	707	1068	2165

3.3 POSTIRRADIATION EXAMINATION OF PHASE I AND PHASE II

The schedule and projected funding for the postirradiation examination of Phases I and II are shown in Table 3.5. The scheduled funding for this examination was a total of \$400K (1989) for each phase, equally shared between U.S. and Japan. Canada will contribute the examination of the Phase II solid specimen. At the end of 1991, \$35K of the available funding for Phase I had been expended on the neutron radiography of the Phase I vented canisters and the nonvented Be enriched-lithium ceramics compatibility canisters. This work was completed at ANL-W.

TABLE 3.5. Projected Funding Schedule for BEATRIX-II Postirradiation Examination (U.S. Dollars, \$K)

Participant	1990	1991	1992	1993	Actual Total	Equivalent 1989 \$K (ANNEX III)
Japan	104	108	(226)		438	400
U.S.		108	(113)	(236)	457	400
Canada				(a)		
TOTAL					895	800
	1.036	1.046	1.045			

(a) Examination of Phase II Solid Specimen.

3.4 FUNDING STATUS

Table 3.6 compares the income versus the expenses for Phase I and Phase II. The total income versus expenses balances out to a -\$242K for the present projected expenditures. This is the same deficit that was projected in the 1990 Annual Report. In an effort to reduce the total costs, the BEATRIX-II Working Group reduced the scope of the Phase II tritium permeation experiment, but additional costs in other areas resulted in no additional savings.

TABLE 3.6. Projected Financial Status for BEATRIX-II, Phase I and II, as of January 1, 1992 (U.S. Dollars, \$K)

	Phase I	Phase II	Total
Income	2675	2180	
Expenses	3542	2165	
Cost Recovery	610		
Difference	-257	+15	-242

4.0 TECHNICAL STATUS

The BEATRIX-II experiment as described in ANNEX-III is divided into Phase I and Phase II. Phase I activities were directed toward FFTF Cycle 11. Irradiation in the FFTF began January 4, 1990, and continued until March 21, 1991, at which time the accumulated exposure was 300 EFPD. Neutron radiography of the Phase I vented canisters and the lithium ceramic-beryllium compatibility capsules was carried out at ANL-W. The Phase II design was established at the final design review held September 1990. Fabrication of the canisters was initiated at this time, and the fabrication and installation of the vented canisters on MOTA-2B was completed in March 1991. Irradiation of BEATRIX-II, Phase II, in FFTF Cycle 12-A.1 started in May 1991. Cycles 12-A.1 and 12-A.2 were completed in September 1991. Cycle 12-B.1 started in November 1991, and was in progress at the end of 1991, with an expected completion date of mid-January 1992.

The BEATRIX-II experiment, including the design and operation of the tritium handling system were described in detail in the previous annual reports (Slagle and Hollenberg 1990b, and 1991; Hollenberg 1989) and other earlier reports (Hollenberg et al. 1989; Puigh et al. 1989; Baker et al. 1991). The tritium measuring system provides capabilities for monitoring the tritium recovered from two in situ tritium solid breeder canisters. Both Phase I and Phase II used the same tritium measuring system. Each gas stream is instrumented to continuously monitor the flow rate, total moisture, tritium concentration, and the form of the tritium. The total tritium concentration and form of the tritium is determined in a manner similar to the VOM experiment (Kurasawa 1986) and uses a ceramic electrolysis cell (CEC) to reduce the water vapor (Konishi et al. 1987) and a molecular sieve trap to remove the water vapor from the sweep gas.

During the two years of operation, the BEATRIX-II experiment has provided an excellent opportunity to advance and improve methods for monitoring and safe handling of tritium during an in situ tritium release experiment. The ionization chambers provided a sensitive record of the tritium recovery with good response times. Although significant shift of zero point occurred

due to background contamination, a procedure has been developed to correct for this shift. The CEC cells have shown some instability when operated for long periods at low water vapor pressures, but this characteristic can be compensated for by reducing the voltage during reactor outages when low water vapor pressures are expected. The tritium getter beds are better than the original design requirements and have successfully reduced the tritium concentration in the sweep gas to acceptable levels for release to the environment.

A general overview of the experiment is contained in the Experimenter's Log, which is a chronological record of the parameter changes that were made during the operation of the experiment. The Experimenter's Log for 1991 is contained in Appendixes A and B for Cycles 11 and 12.

The complete data set was continuously monitored and stored on data disks at the experiment site at the FFTF. This data was provided to the experiment coordinator (PNL) who then transferred the data to JAERI, AECL, and ANL-E.

4.1 BEATRIX-II, PHASE I

The BEATRIX-II, Phase I experiment, has been described in detail in the previous annual reports (Hollenberg 1989; Slagle and Hollenberg 1990b, and 1991) and earlier reports (Hollenberg et al. 1989; Puigh 1988; Baker et al. 1991). The ring specimen capsule was designed to operate as a temperature-change canister in a manner similar to several previous tritium recovery experiments (e.g., TRIO [Clemmer et al. 1984], VOM [Kurasawa 1986], CRITIC [Verrall 1988]) while the solid specimen capsule provides performance data on Li_2O irradiated in a temperature gradient.

The specimen descriptions and the irradiation conditions are given in Table 4.1. The ring specimen has a wall thickness of 0.16 cm with thermocouples located at the inner and outer surfaces. The temperature of the ring specimen was controlled by changing the type of gas in the thermal gap of the canister (Slagle and Hollenberg 1990b; Hollenberg et al. 1989). The solid specimen is a stack of 11 pellets with densities that range from 84.5 to 92.6% of theoretical density (TD). The end pellets in the stack have a center annulus for insertion of centerline thermocouples. The solid specimen is not

TABLE 4.1. Materials and Environmental Conditions for BEATRIX-II

Specimen Characteristics	Ring	Solid
Length (cm)	8.90	8.92
Outer dia. (cm)	1.84	1.70
Inner dia. (cm)	1.51	0.27
Weight (g)	11.95	34.31
Density (%TD)	79.3	84.5-92.6
Grain size (microns)	5.5	46
⁶ Li (at %)	61	61
Measured Temperature (°C):		
• Center	540-640	1000
• Edge	500-600	450
Tritium Generation Rate (10 ⁻⁶ Ci/s):		
• Predicted	47	124
• Measured	44.6	110
Predicted Total Generation:		
• 300 EFPD (Ci)	1150	2850
Predicted Fluence:		
• 300 EFPD (10 ²² n/cm ²) (E > 0.1 MEV)	3.9	3.9

temperature controlled, and has an edge temperature of 450°C and a center temperature of 1000°C. For a 300-EFPD irradiation, the goal burnup was 4% of the total lithium for both specimens.

4.1.1 Phase I: Temperature-Change Canister

Testing of the Phase I temperature-change canister in 1991 involved irradiation in FFTF Cycle 11-C. Startup of this cycle occurred at the end of 1990. The startup was not carried out in the normal reference sweep gas of He-0.1%H₂ but rather in a helium sweep gas. Startup in helium completed the second phase of a study on the effect of helium sweep gas on the tritium recovery during a changing neutron flux. The first phase was initiated at the end of Cycle 11-B.2 when the test was shutdown in helium.

Testing of the temperature-change canister during Cycle 11-C involved 1) determining the effect of a series of temperature changes on the tritium recovery rate in each of the three sweep gases: He, He-0.1%H₂, and He-0.01%H₂; 2) making a series of sweep gas composition changes at 550 and 650°C in the sequence of He-0.1%H₂, 2 days in He-0.01%H₂, 4 days in He, He-0.1%H₂; and 3) completing a series of temperature changes to characterize the effect of burnup at the end of the irradiation (290 EFPD). A complete description of the test plan is included in Appendix A.

4.1.1.1 Temperature/Gas Composition

The effect of temperature and temperature change on the tritium recovery rate was characterized using a sequence of temperature changes in the order of 650-600-550-600-650-550-650°C. The effect of sweep gas composition on the tritium recovery during this temperature sequence was studied in each of the three sweep gases: He-0.1%H₂, He-0.01%H₂ and He. Figure 4.1 compares recovery curves for a temperature change from 550 to 650°C in the three different sweep gases. For the sweep gas He-0.1%H₂ the change in tritium inventory during the temperature change was the smallest of the three gases. The tritium recovery peak for this sweep gas (He-0.1%H₂) consists of two peaks, whereas the recovery curves for He and He-0.01%H₂ are single peaks that are similar to each other in shape and size. The double peak for He-0.1%H₂ is similar to that determined by Kurasawa et al. (1991). The first peak is associated with the recovery of the reduced form of tritium, HT, and the second peak is associated with the oxidized form, HTO. This suggests that for the sweep gases containing lower concentrations of hydrogen, the recovered tritium occurs predominately in the reduced form.

FIGURE 4.1. Tritium Concentration for the Phase I Temperature-Change Canister During Temperature Changes from 550 to 650°C in Sweep Gas Compositions of He-0.1% H_2 , He-0.01% H_2 , and He

4.1.1.2 Gas Composition/Temperature

The effect of gas composition on tritium recovery was measured by varying the gas composition between three different concentrations of hydrogen in the helium sweep gas: 0, 0.01%, and 0.1%. The temperature dependence of the gas composition dependence was studied by carrying out the gas composition changes at 550 and 650°C.

A series of gas changes were carried out in sequence of He-0.1% H_2 , two, four or eight days in He, three days in He-0.01% H_2 , then finally back to

He-0.1% H_2 . These gas composition changes were carried out at 550 and 650°C. These test were carried out in Cycle 11-B.2 and were reported by Slagle and Hollenberg (1991).

A more abbreviated series of gas changes were carried out in Cycle 11-C in sequence of He-0.1% H_2 , two days in He-0.01% H_2 , four days in He, He-0.1% H_2 . The tritium recovery curves obtained are shown in Figure 4.2. The tritium recovery curves at 550 and 650°C are very similar to each other, with decreasing recovery rates after the gas-change transitions from He-0.1% H_2 to He-0.01% H_2 and from He-0.01% H_2 to He, and with a tritium recovery peak for the transition from He to He-0.1% H_2 . The primary difference is that at the higher temperature the recovery curves approached steady state faster, and the final recovery peaks for the transition from He to He-0.1% H_2 were sharper and occurred in a shorter period.

4.1.1.3 Burnup Effects

A series of temperature changes in the order of 650-600-550-650-550-650°C were carried out at different times to characterize the effect of burnup in He-0.1% H_2 . This was done after irradiation periods of 80, 215, and 290 EFPD. Figure 4.3 compares the tritium recovery curves measured during the final 550 to 650°C temperature change in the sequence, as observed at the three different burnups. In general, it was found that early in the experiment a double peak was associated with a temperature change. This double peak transformed towards a single peak as the experiment progressed with increasing burnup. Since the first peak is due to the recovery of HT and the second is due to HTO, the observed change suggests that the amount of HTO recovered relative to amount of HT recovered decreases with increasing burnup for a given temperature change. The change in peak shape was observed as a function of burnup. However, it is possible that the observed change in peak shape could also be related to moisture reduction either in the Li_2O specimen or in the tritium sweep gas system between the specimen and the ionization chamber.

4.1.1.4 Reactor Shutdown and Startup

Reactor shutdown and startup sequences provide opportunities to study the effect of changes in the tritium generation rate (neutron flux) and

FIGURE 4.2. Tritium Concentration for the Phase I Temperature-Change Canister During Sweep Gas Composition Changes of He-0.1%H₂, 2 Days in He-0.01%H₂, 4 Days in He, He-0.01%H₂, at 550 and 650°C

g0058-01.SP5 08/17/92

FIGURE 4.3. Tritium Concentration for the Phase I Temperature-Change Canister During Temperature Changes from 550 to 650°C After Irradiation Periods of 80, 215, and 290 EFPD

temperature on tritium recovery from the temperature-change canister. The effect of gas composition on the behavior of the specimen under a changing neutron flux was studied during reactor startup and shutdown. Normally shutdowns/startups were carried out in the reference gas of He-0.1% H_2 but the effect of sweep gas composition on the behavior was studied by placing the specimen in helium sweep gas for two days before the shutdown of the second operational cycle (Cycle 11-B.2) and then again using the helium sweep gas through the startup of the third operational cycle (Cycle 11-C). This occurred during 1990, and the results for the temperature-gradient canister were reported by Slagle and Hollenberg (1991). The results for the temperature-change canister were not reported in the 1990 Annual Report

because they had not yet been analyzed at the time. Since then, the behavior has been studied and reported at ICFRM-5 (Slagle et al. 1991) and are included in the current annual.

During reactor startup/shutdown in reference gas, He-0.1% H₂, the observed tritium recovery curves are very similar to the temperature curves for the inner diameter of the specimen. This is as expected because the temperature is related directly to heat (tritium) generation, and tritium recovery is related directly to tritium generation. However, using helium as a sweep gas during reactor shutdown significantly affected the observed tritium recovery behavior. Figure 4.4 compares the recovered tritium during

FIGURE 4.4. Recovered Tritium Concentration and Temperature of the Phase I Temperature-Control Canister During a Reactor Shutdown in a Helium Sweep Gas

the reactor shutdowns in helium with the inner specimen temperature. As the neutron flux decreased, the specimen temperature and the recovered tritium both initially decreased as the tritium generation rate decreased, but later the recovered tritium concentration increased in direct contrast to the continual decrease in the generation rate. The increase in the tritium recovery with decreasing temperature first occurred between an inner specimen temperature of 500 and 475°C. This behavior continued until the inner temperature of 350°C was reached.

The tritium recovery behavior during reactor startup in helium was found to be different than observed in He-0.1% H₂. Because the power increases during startup were in larger increments than those during shutdown, the change in behavior is not as distinctive. However, an increase in neutron flux and temperature at approximately 500 to 525°C resulted in a decrease in the recovered tritium. Above 525°C the tritium recovery rate increased with increasing neutron flux.

The anomalous tritium recovery behavior of the temperature-change canister during shutdown and startup in helium occurs in a temperature range near the melting point of LiOH. In this temperature range, the presence of LiOH is an important factor in determining the tritium inventory (Billone et al. 1991; Tetenbaum and Johnson 1984). The present tritium recovery observations involve LiOH behavior and could be explained by LiOH dissolution in Li₂O and the variation of the water vapor pressure over LiOH dissolved in Li₂O.

Because the moisture levels in the sweep gas are typically less than 0.1 Pa, it is expected that the amount of LiOH in the specimen remains below the solubility limit as the temperature is decreased. Therefore, LiOH dissolution in Li₂O is not expected to be a factor in the tritium recovery.

An alternative explanation is associated with the water vapor pressure associated with LiOH dissolved in Li₂O. The results of a study by Norman and Hightower (1984) indicate that for stable solid solutions of LiOH in Li₂O, i.e., less than the solubility limits, the water vapor pressure curves versus temperature curves exhibit a maximum in the temperature range below the two-phase boundary. That is, for a given amount of LiOH dissolved in Li₂O, at a

temperature less than the two-phase boundary, a temperature decrease results in an increase in the equilibrium water vapor pressure. After reaching a maximum, a further decrease in temperature results in a decrease in the water vapor pressure. The observed peak in the tritium recovery curve during shutdown could then be associated with this peak in the water vapor pressure with decreasing temperature that results from the LiOH (or LiOT) dissolved in Li₂O. It is to be noted that the temperature at which this peak occurs increases with decreasing dissolved LiOH (LiOT).

4.1.1.5 Temperature/Neutron Fluence Change in Helium Sweep Gas

Changes in the specimen temperature, either from changes in the thermal gap of the capsule (Figure 4.1) or from changes in neutron flux (Figure 4.4), produced larger changes in tritium inventory when the sweep gas was helium instead of He-0.1% H₂. In these data, the peak in the tritium recovery during shutdown occurs in the temperature region near 500°C because the peak is probably related to LiOH dissolved in Li₂O. In the previous annual report (Slagle and Hollenberg 1991), a similar behavior was reported for the temperature-gradient specimen when shutdown occurred in He. However, the recovery peak for the temperature gradient specimen was associated with much higher temperatures, and the behavior was attributed to tritium/hydrogen dissolved in the lattice.

One difference between helium sweep gas and He-0.1% H₂ sweep gas is the tritium/hydrogen ratio. A tritium concentration of 25 Ci/m³ in He-0.1% H₂ is equivalent to a tritium/hydrogen ratio of approximately 1/100. In a helium sweep gas, where only trace amounts of hydrogen are present, the tritium/hydrogen ratio becomes very large. If the Li₂O specimen is in equilibrium with the sweep gas it is expected that the same tritium/hydrogen ratio would be associated with tritium/hydrogen dissolved in the bulk of the material and with the tritium/hydrogen adsorbed on the surface. On this basis, a larger tritium inventory is expected in a helium sweep gas and thus larger changes in the inventory are possible. This line of reasoning can only serve as a first approximation, however, since the total amount of tritium/hydrogen in the specimen would be expected to be less for lower hydrogen partial pressures such as in a helium sweep gas.

Sweep gas composition changes affected the tritium recovery significantly more than temperature change. This suggests that the interaction of gas and solid is more important than the thermally activated diffusion processes.

4.1.1.6 Conclusions

The results of the BEATRIX-II, Phase I irradiation experiment have provided an extensive data base on tritium recovery that gives insight into the in situ tritium release characteristics of Li_2O for lithium burnups to 5%. The particular implications of the results are as follows:

1. Decreasing the temperature directly affects the shape/size of the tritium recovery peaks observed during gas composition changes involving an increase in the hydrogen concentration. In several instances, the lower temperatures gave delayed recovery peaks.
2. In general, reducing the amount of hydrogen in the helium sweep gas resulted in a larger change in tritium inventory during a given temperature transient and also resulted in a higher percentage of the recovered tritium being in the reduced form (HT).
3. The form of the tritium recovered, that is the amount of HT versus HTO, during a given temperature transient was found to change during the experiment. Specifically, the amount of HTO decreased with increasing burnup and/or operating time. This could be due to burnup effects in the specimen but alternatively may result from changes in the tritium handling system such as lower surface moisture.
4. The tritium recovery during startup and shutdown was strongly influenced by the composition of the sweep gas.

4.1.2 Phase I: Temperature-Gradient Canister

The two primary experimental parameters available for studying the performance of the solid or temperature-gradient specimen were the neutron flux, which changed during reactor startup/shutdown, and the sweep gas, which has variable composition and flow rate.

Three subcycles: 11-B.1 (85 EFPD), 11-B.2 (134 EFPD) and 11-C (81 EFPD), provided essentially constant reactor power levels. Results of the first two subcycles were presented in the previous annual report. The experimental test plan for the temperature-gradient specimen for Cycle 11-C is

detailed in the Experimenter's Log in Appendix A and is summarized in Table 4.2. In Table 4.2, the sweep gas composition change represents a change in composition from the reference condition, which was a sweep gas of He-0.1% H₂, to an alternative sweep gas as listed in the table.

4.1.2.1 Temperature History

One of the directly observable indicators of the physical stability of the solid specimen was the long-term stability of the specimen's temperature during irradiation. Figure 4.5 is a plot of the temperatures from the two centerline thermocouples for the entire 300 EFPD. The top thermocouple is at a higher temperature because it was closer to the center of the reactor core and, therefore, was in a region of higher neutron flux. Also included in Figure 4.5 are notes on reactor operation which affected the temperature of the specimen. When the test was first taken to full power, the reactor operated at 95% power before increasing in power to 100%. During the first ten days of operation, after reaching 95% power, the temperature of both thermocouples appeared to drop, with the top thermocouple temperature dropping as much as 30°C. Other than this initial drop there was, in general, only a slow steady decrease in the temperatures throughout the reactor cycle, both at 95% and 100% power. This temperature drop can be partially attributed to a slow

TABLE 4.2. Experimental Test Plan for the Solid Li₂O Specimen During FFTF Cycle 11-C. Parameter changes indicate changes in composition from the reference condition, which was a sweep gas of He-0.1% H₂, to an alternative sweep gas.

Test No. Cycle 11-C	Parameter Change from Reference State Duration in days (d)
12	Reactor startup followed by He (1d) plus He-0.01% H ₂ (2d)
13	He (4d) plus He-0.01% H ₂ (6d)
14	He (8d) plus He-0.01% H ₂ (2d)- reactor shutdown
15	He-1.0% H ₂ (1d)

39109041.1

FIGURE 4.5. Center Temperatures for the Temperature-Gradient Capsule During Phase I Irradiation

decrease in the neutron flux at the capsule as the reactor control rods were pulled out to maintain constant power with fuel burnout.

For the first operational cycle, Cycle 11-B.1, when the reactor reached 100% power, the average inner temperature was 998°C, dropping to 952°C at the end of the cycle. In the two successive reactor cycles, a similar type of behavior was observed. In Cycle 11-B-2, the average inner temperature at 100% power dropped from an initial temperature of 1006°C to 961°C at the end of the 134 EFPD cycle. For Cycle 11-C the temperature dropped from an initial temperature of 1027°C to 995°C after an 81 EFPD cycle. The temperature difference between cycles resulted from the change in neutron environment brought about by the refueling that occurred between cycles.

There is the possibility that radial thermal gradients could cause fracturing of the specimen and increase the temperature difference across the specimen. This would result in an increase in the measured centerline temperatures. The initial steep drop in temperatures at the very start of the experiment may indicate that some restructuring in the specimen has occurred but is not indicative of any internal fracturing. From the typically observed, slowly decreasing temperatures it is inferred that the microstructure of the specimen remained relatively stable and did not undergo any drastic changes such as thermal-shock fracturing. Postirradiation examination will provide the final assessment of the microstructural changes that have occurred during the experiment.

4.1.2.2 Sweep Gas Composition Effects

Sweep gas composition, in particular the amount of H_2 in He, was found to have a major effect on the steady-state tritium recovery. Determining this effect was the primary objective of the test plan in Table 4.2.

In the previous annual report (Slagle and Hollenberg 1991) sweep gas compositions were reported for changes in sweep gas from the reference gas of He-0.1% H_2 to an alternative gas containing less H_2 for the first and second cycle. These alternative sweep-gases were He-0.01% H_2 and pure He. In the first test cycle, the alternative gases were used for a duration of two days. For the second cycle the two-day tests were repeated and then extended to four

days. The next series of tests involved a combination of alternative gases in the sequence of He-0.1% H₂, He, He-0.01% H₂ to He-0.1% H₂. During Cycle 11-B.2, the duration times in the two alternative gases (He and He-0.01% H₂) was varied from two to four days.

The tritium recovery curves obtained in Cycles 11-B.1 and 11-B.2 (see previous annual report) (Slagle and Hollenberg 1991) exhibited a baseline tritium recovery rate that appeared to increase with increasing time, despite transitions from He to He-0.01% H₂. This suggests that with longer times the recovery rate in He-0.01% H₂ would have approached the recovery rate in He-0.1% H₂. To test this hypothesis, two additional tests, #13 and #14, were carried out for extended times in alternative gases. The resulting curves of recovered tritium are shown in Figure 4.6. Test #13 was run four days in helium and then for six days in He-0.01% H₂. The resulting recovery rate in He-0.01% H₂ at the end of this run (after subtracting the background) was 78% of the recovery rate in reference gas at the start of this test. Test #14 was run with an even longer time in He, extending the time to eight days. After two days in He-0.01% H₂ the recovery rate was 83% of the recovery rate in reference gas at the start.

It is concluded from the results of Tests #13 and 14 with the alternative sweep gases, that for periods up to 10 days, the observed recovery rates were always less than the recovery rates in reference gas. One possible explanation is that the release rate from the specimen was less than the generation rate and a buildup of tritium was occurring in the specimen or that tritium was accumulating in other regions of the system. The continuation of this low recovery rate for an indefinite period suggests that the specimen tritium inventory was changing. The reduction in recovery rates with lower concentrations of hydrogen in the sweep gas has also been observed in the VOM experiment (Kurasawa et al. 1986). In the CRITIC-1 test on Li₂O (Verrall et al. 1988), this effect was not seen directly, but was inferred from a buildup in the tritium inventory over long periods using low H₂ concentrations in the sweep gas.

The significant changes in tritium recovery observed by decreasing the hydrogen in the sweep gas to less than 0.1% H₂ suggested that an increase in

G0043 WO1 03 04/02/91

FIGURE 4.6. Tritium Recovery Concentrations During Sweep Gas Composition Changes in the Phase I Temperature-Gradient Specimen for Tests #13 and #14

hydrogen should be considered. Test #15 was carried out using He-1% H₂ as the sweep gas. The results are shown in Figure 4.7. For the change from He-0.1% H₂ to He-1.0% H₂, there was an initial decrease in the recovered tritium concentration followed by a small peak and an approach to steady state. This increase in the apparent steady-state recovery in He-1.0% H₂ was 21% of the initial measured recovery rate (corrected for background) in the reference sweep gas.

The increase in the apparent recovery rate in He-1.0% H₂ versus the reference gas has significant implications. One possible explanation is that the recovery rate for the reference sweep gas of He-0.1% H₂ was less than the generation rate. Another possible explanation is that the response of the ionization chambers is not independent of the H₂ content of the gas, and the addition of H₂ results in a higher indicated concentration of tritium. This would also explain the failure for the recovery rates in the alternative gases with lower H₂ concentrations to reach the recovery rate in the reference gas. The possibility of the ionization chamber response being affected by the gas composition will be characterized in future testing and this will be discussed in later sections of the report. (See 4.1.2.3 Tritium Balance Calculations and 4.4 Data Transfer.)

In addition to changes in the tritium recovery rate for a sweep gas of He-1.0% H₂, the moisture in the recovered sweep gas increased from 25 ppm for the reference gas to 440 ppm for He-1 0% H₂. This moisture level was much higher than observed previously during the experiment. The recovered HTO did not show any comparable increase and was proportional to the total recovered tritium curve. Because of the overwhelming large amount of hydrogen compared to tritium (300:1), it is difficult to draw any conclusions as to whether this moisture was released from the specimen or from other components of the system.

4.1.2.3 Tritium Balance Calculations

As described in the previous sections, the sweep gases used in BEATRIX-II are helium with four different concentrations of hydrogen: 0, 0.01%, 0.1% and 1.0%. He-0.1% H₂ is the reference gas and the majority of the testing is carried out using this gas composition. Decreasing the hydrogen concentration

G0054 WC1 (A) (4) 12 91

FIGURE 4.7. Tritium Recovery Concentrations and Sweep Gas Moisture for a Change from He-0.1% H_2 to He-1% H_2 Sweep Gas Through the Phase I Temperature-Gradient Specimen (Test #15)

in the sweep gas has in all cases decreased the measured tritium recovery rate. When first observed, this decrease was attributed to a decrease in the tritium recovery rate from the system (Kurasawa et al. 1991). However three different subsequent observations suggested that the changes in the measured recovery were due to something else. These observations were:

1. Testing for long periods (up to 10 days) in hydrogen concentrations less than 0.1% led to pseudo steady-state recovery rates that were less than the recovery rates in the He-0.1% H₂ (see Figure 4.6). This implies that there is a continual build up of tritium inventory in the sample and that steady-state is never reached.
2. Increasing the hydrogen concentration from 0.1% to 1% led to an even higher (20% higher) steady-state tritium recovery rate (see Figure 4.7). Since the recovery rate in He-0.1% H₂ was in good agreement with the calculated generation rate, it was assumed that the recovery rate in this sweep gas was equal to the generation rate. A steady-state recovery rate in He-1.0% H₂ greater than the previously assumed generation rate was difficult to explain.
3. Changes in the sweep gas composition during periods when no tritium was being generated (after reactor shutdown at the end of Cycle 11-C) resulted in an increase in the background readings for the ion chambers as the hydrogen concentration was increased. Table 4.3 lists the background readings for the five different ion chambers in the three different sweep gases: He-0.1% H₂, He-0.01% H₂ and He. The background in He-0.1% H₂, relative to that for He-0.01% H₂ and He is given in the last two columns. This increase ranges from 1.27 to 1.32 for helium and from 1.22 to 1.26 for He-0.01% H₂. These changes were observed to be reversible and

TABLE 4.3. Effect of Sweep Gas Composition on Ion Chamber Background

Ion Chamber	Background Reading			Reference/Alternative		
	0.1% H ₂	0.01% H ₂	He	0.1% H ₂	0.01% H ₂	He
Ring Specimen						
• CEC	10.00	7.91	7.58	1	1.26	1.32
• Mol Sieve	3.49	2.79	2.66	1	1.25	1.31
Solid Specimen						
• CEC	17.92	14.72	14.16	1	1.22	1.27
• Mol Sieve	13.79	10.99	10.62	1	1.26	1.30
Getter Bed	4.88	3.94	3.74	1	1.24	1.30

indicated that the changes were not due to changes in the ion chamber but only changes to the response.

One possible explanation for the observed change in the recovery rates resulting from a change in sweep gas composition is that the ion chamber response is dependent on sweep gas composition. The role of the ion chamber response on the recovery rates as a function of sweep gas composition was investigated by a further analysis of a series of tritium recovery curves obtained for the temperature-gradient specimen. These series of tritium recovery curves were from Cycle 11-B.2 and 11-C. The three series were as follows:

1. The test series from Cycle 11-B.2 starting in He-0.1% H_2 then changed to helium for four days and then returned to He-0.1% H_2 .
2. The test series from Cycle 11-B.2 starting in He-0.1% H_2 then changed to He-0.01% H_2 for four days and then returned to He-0.1% H_2 .
3. The test series #13 from Cycle 11-C (see Figure 4.6) starting in He-0.1% H_2 then changed to He for 4 days, then to He-0.01% H_2 for six days and then returned to He-0.1% H_2 .

An integration of the tritium recovery curves were carried out to determine the amount of tritium inventory that was stored in the specimen during operation in sweep gases with hydrogen concentrations less than 0.1%. This increase in inventory was then compared with the decrease in inventory observed when the hydrogen concentration was increased to 0.1%. In order to determine the possible effect of the ion chamber response being affected by the composition of the sweep gas, the factors given in Table 4.1 were used to compensate for the reduction in response for lower hydrogen concentrations. The values for the temperature-gradient canister-CEC ion chamber were used in the calculations. Specifically, these values were 1.27 for helium and 1.22 for He-0.01% H_2 .

Figure 4.8 is a compilation of the curves resulting from the integration of a test series #1 which started in He-0.1% H_2 then changed to helium for four days and then returned to He-0.1% H_2 . The five curves in Figure 4.8 can be described as follows:

INTEG-1C.SP5 02/08/14

FIGURE 4.8. Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in a Helium Sweep Gas (Series #1). Calculations carried out using ion chamber response "as-measured" and "compensated" for sweep gas composition.

Recovered Tritium Concentration (Ci/m³):

As-Measured. This is the tritium concentration as measured by the ion chamber with a background correction.

Compensated. This is the as-measured tritium concentration with a compensation factor of 1.27 for operation in helium. This factor was determined from the change in ion chamber background (Table 4.1) observed when the sweep gas was changed from He to He-0.1% H₂.

Total Tritium Recovery (Ci):

As-Measured. This curve is the result of an integration of the as-measured recovered tritium concentration as a function of time.

Compensated. This curve is the result of an integration of the compensated recovered tritium concentration as a function of time.

Generated. This curve is the total amount of tritium that was generated during this period, assuming that the generation rate was equal to the initial tritium recovery rate in He-0.1% H₂.

A comparison of the total recovered tritium for the as-measured curve and for the generated curve indicates that upon returning to He-0.1% H₂ an increase in the tritium inventory in the specimen occurred compared to the previous inventory in He-0.1% H₂. In contrast, the total recovered tritium for the compensated curve is in good agreement with the integration of the generation rate. This indicates that the inventory in the specimen at the end of the test is the same as at the start of the test.

The analysis shown in Figure 4.8 was repeated for the other two test series. The results for Series # 2, which was four days in He-0.01% H₂, are given in Figure 4.9. The results for Series #3, which were four days in He and six days in He-0.01% H₂, are given in Figure 4.10. For both tests, the integration results indicate that the total recovered tritium for the compensated curves is in good agreement with the integration of the generation rate. This agreement suggests that the inventory in the specimen at the start of the test is nearly the same as at the end of the test.

It is concluded from the results of this analysis that the BEATRIX-II ion chamber response could be affected by sweep gas composition. The results also suggest that if increasing hydrogen in the sweep gas is assumed to

INTEG-2.SP5 08/17/92

FIGURE 4.9. Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in a He-0.01% H_2 Sweep Gas (Series #2). Calculations carried out using ion chamber response "as-measured" and "compensated" for sweep gas composition.

INTEG-3.SP5 08/17/92

FIGURE 4.10. Total Tritium Recovered from the Phase I Temperature-Gradient Canister During 4 Days of Operation in Helium and 6 Days in He-0.01% H_2 Sweep Gas (Series #3). Calculations carried out using ion chamber response "as-measured" and "compensated" for sweep gas composition.

increase the apparent response of the ion chamber, then it is possible to obtain a consistent explanation of the BEATRIX-II results of tritium recovery as a function of gas composition.

4.1.2.4 Conclusions

The BEATRIX-II, Phase I experiment provided data for in situ tritium recovery from a Li_2O specimen irradiated under a large thermal gradient typical of fusion blanket designs. This test has provided additional verification of the viability of Li_2O as a candidate for a fusion solid blanket. Results from the 300 EFPD of operation can be summarized as follows:

1. Throughout the 300 EFPD of irradiation, the temperature of the specimen was nearly constant or decreased slowly. From the stability of the temperature it is inferred that the microstructure and the thermal properties of the specimen have also remained stable and that the specimen has remained physically intact.
2. The composition of the sweep gas was found to be a critical parameter in the recovery of tritium from Li_2O . In general, decreasing/increasing the amount of hydrogen in the sweep gas appeared to decreased/increased the recovery rate of tritium. For sweep gases having smaller amounts of H_2 than the reference gas, the apparent recovery rates are always less than the recovery rates in reference gas for periods up to 10 days. However, it would appear that this effect of sweep gas composition on recovery rate is due almost entirely to the effect of sweep gas composition on response of the ionization chambers. Ion chamber response appears to be dependent on the sweep gas composition with additions of 0.01 and 0.1 and 1% hydrogen to the sweep gas giving progressively higher response.

4.1.3 Phase I: PIE - Radiographs

The Phase I vented canisters were removed from the MOTA irradiation vehicle in April 1991, and shipped to Argonne National Laboratory-West (ANL-W) in May of 1991, for neutron radiography. The first series of radiographs were completed in June 1991, but selected radiographs were repeated during the October to December 1991, period.

Figure 4.11 is the radiograph of the temperature-change canister after irradiation. It appears that the specimen remained largely in place during irradiation, but there is an extensive amount of cracking that can be seen. One anomalous observation is the occurrence of some neutron absorbing material below the specimen underneath the diffuser plate through which the sweep gas

FIGURE 4.11. Neutron Radiograph of Phase I Temperature-Change Canister After Irradiation

enters the capsule. A more subtle observation is the variation in darkness along the length of the specimen suggesting that the thickness may not be uniform as would be the case if material fell off the inside diameter.

Figure 4.12 is a radiograph of the temperature-gradient canister. The thickness of the specimen makes it nearly impossible to determine any internal structure in the specimen. The ends of the enriched pellet column appears to be domed upward as if the hotter inner portion of the pellet stack swelled and increased in length. The insulator pellets, which were initially depleted Li_2O , appear to have become enriched during irradiation. The lower pellet has a gradation in darkness being darkest at the top where it was adjacent to the enriched pellet and darker near the center where it was hotter. This type behavior was seen previously in the large diameter Li_2O pellets irradiated in the FUBR-1B irradiation test in EBR-II (Slagle and Hollenberg 1990a). The upper depleted pellet is darker than the lower insulator pellet but there does not appear to be a gradation of lithium enrichment. Evidently the higher temperature at the top of the specimen column resulted in greater lithium-6 transport to the extent that there was very little final gradient in the lithium-6 concentration.

4.2 BEATRIX-II, PHASE II FABRICATION

Phase II of the BEATRIX-II experiment involved the irradiation of a Li_2O ring specimen and a Li_2ZrO_3 solid specimen, the latter in the form of a sphere bed. The Phase I Li_2O ring specimen was prepared in the U.S.; the ring specimen for Phase II was prepared in Japan. Improved fabrication techniques resulted in a higher density, larger grain size material which together with a sophisticated machining capability resulted in the fabrication of a ring specimen with a thinner wall. Li_2ZrO_3 was chosen as the alternative ternary breeder material most suitable for additional characterization. In previous vented (Briec et al. 1988) and non-vented (Slagle, Hollenberg, and Baldwin 1991; Hollenberg and Baldwin 1985) tests, Li_2ZrO_3 had been found to be dimensionally and chemically stable during irradiations and to have relatively short tritium residence times. The material used was 1-1.5 mm diameter

FIGURE 4.12. Neutron Radiograph of Phase I Temperature-Gradient Canister After Irradiation

Li_2ZrO_3 spheres prepared by AECL Research. An additional objective for Phase II was to reach lithium burnups of 8%, twice that of Phase I.

4.2.1 Temperature-Change Canister

The Phase II temperature-change canister is nearly identical to the Phase I temperature-change canister. The primary emphasis is to reach higher burnups and achieve a lower minimum temperature. These requirements and some desired improvements found necessary during the operation of Phase I, presented a challenge to the designer.

The design requirements for the Phase II temperature-change specimen were very similar to those for Phase I and included considerations such as the sensitivity of tritium measurements, minimizing the loss of tritium to the reactor, and the temperature of the specimen. A major change in the requirements was the increase in lithium burnup from 4 to 8%. This was partially achieved by increasing the ^6Li enrichment from 61 to 95 at%. However, this increase in enrichment and, subsequently, in the heating rate makes it even more difficult to attain lower temperatures desired in Phase II. To offset such an increase in heating rate, the total amount of ^6Li , and, thus the heating rate, in the specimen was kept constant by decreasing the volume. Specifically, the wall thickness of the ring specimen was decreased from 0.15 cm in Phase I to 0.10 cm in Phase II. Table 4.4 summarizes a description of the Phase II temperature-change canister and the predicted operating parameters of the canister. The Phase II ring specimen was a single section of tube, 8.85 cm long in contrast to the Phase I specimen, which consisted of two sections. The final density was determined to be 87.3% TD with a grain size of 22 μm . The design of the Phase II temperature-change canister is described in detail in the previous annual report (Slagle and Hollenberg 1991).

Figure 4.13 shows the temperature change capsule with the ring specimen in place, the "backup" specimen, and the inner perforated sleeve prior to final loading. The specimen slid easily into the capsule, which had an inner diameter of 1.863 cm or a 0.010 cm diametral clearance. The Phase I capsule used an inner sleeve of nickel screen, but for Phase II this was replaced by a perforated stainless steel tube. Stainless steel was used to minimize the types of metal surfaces in contact with the purge gas. A perforated tube was

TABLE 4.4. Description of BEATRIX-II, Phase II Ring Specimen/Canister

⁶ Li Enrichment	95 at%
Outer Diameter	1.850 cm
Wall Thickness	0.10 cm
Length	8.85 cm
Weight	8.103 g
Density	87.3% TD
Grain Size	22 μ
Specimen Minimum Temperature Outer Diameter Inner Diameter	485°C 503°C
Tritium Generation(300 EFPD)	1250 Ci
Total Lithium Burnup	7.8 at%

chosen over the screen because of problems in Phase I with thermocouple location. The tube was a more rigid structure than the screen used previously and allowed a more definite positioning of the thermocouples.

Figure 4.14 is an X-ray radiograph of the capsule after loading. This shows clearly the relationship of the different components. The correct positioning of the inner thermocouples in the slots provided by the inner sleeve can be seen. The thermocouple in the center of the radiograph is the outer thermocouple which measures the temperature in the sodium used as a thermal contact. The assembly shown in Figure 4.14 was thermally bonded with sodium inside the gas-gapped thermally controlled canister. The sodium serves to minimize axial temperature gradients.

4.2.2 Temperature-Gradient Canister

The material in the temperature-gradient canister was chosen to be a Li_2ZrO_3 monosized sphere bed. This "solid" specimen with its inherent

39103138.4

FIGURE 4.13. Phase II Temperature-Change Capsule with the Loaded Specimen, the "Backup" Specimen, and the Inner Perforated Tube before Final Assembly

39103138.3

FIGURE 4.14. X-Ray Radiograph of the Phase II Temperature-Change Canister As-Fabricated

temperature gradient is similar in overall design to the Li_2O specimen used in Phase I and provides a comparison for evaluating the relative merits of the two breeder forms proposed for fusion blanket applications. The sphere diameters were specified to be in the range from 1-1.5 mm with a ^6Li enrichment of 85 at% and were provided by AECL Research. A description of the sphere bed is given in Table 4.5.

The desired centerline temperature in the sphere bed was within the range from 1000 to 1200°C. These limits were chosen based on the desire to obtain data at temperatures as high as possible, without changing the microstructure of the lithium zirconate. Confirming the reliability of the solid breeder material over a broad range of temperatures minimizes the design restrictions imposed in the future when actual blanket designs are being considered. Achieving these temperatures is a function of the neutron environment and the diameter of the sphere bed or capsule. The predicted temperatures and tritium production is given in Table 4.5.

The Li_2ZrO_3 spheres were fabricated by AECL Research. The diameters of the slightly non-spherical Li_2ZrO_3 spheres fall approximately in the range of

TABLE 4.5. Predicted Thermal and Neutronic Performance of the BEATRIX-II Li_2ZrO_3 Sphere Bed Canister

Properties of the Sphere Bed: • Sphere Diameter • ^6Li Enrichment • Sphere Matrix Density • Sphere Packing Density • Outer Diameter • Inner Diameter • Total Weight	1-1.5 mm 85 at% 80% TD 60% 1.32 cm 0.23 cm 29.47 g
Specimen Centerline Temperature: • Maximum • Minimum	1160°C 1030°C
Tritium Generation (300 EFPD)	828 Ci
Total Lithium Burnup	8.9 at%

1 to 1.5 mm with a nominal diameter of 1.2 mm. Figure 4.15 shows the top of the sphere bed as loaded into the temperature-gradient canister. This view gives an indication of the sphere diameters relative to the capsule dimensions. The center tube is the thermal well into which the upper thermocouple was inserted to complete the assembly.

Prior to loading, the spheres were vibrated into volumes from 2.0 to 6.0 cm³. As indicated above, packing densities of 60% are expected for these spheres in the volumes involved. The resulting packing densities ranged from 2.03 to 2.08 g/cm³. The capsule was loaded by vibrating 29.47 g of spheres into a volume of 13.75 cm³ volume. The resultant density was 2.143 g/cm³. Assuming the density of the individual spheres is 80% TD (TD = 4.112 g/cm³) implies that an actual packing density of 65.1% was achieved. Such a high packing density may be attributable to the deviation of the material from perfect spheres and/or to the density of the individual spheres being larger than 80% TD.

FIGURE 4.15. Li_2ZrO_3 Spheres As-Loaded in the Phase II Temperature-Gradient Canister

The higher density of Li_2ZrO_3 in the capsule is not expected to significantly change the resulting temperature distribution. The increase in heat generation from the higher ^6Li loading is offset by the anticipated increase in thermal conductivity. The resulting centerline temperatures achieved during the irradiation testing can be compared with the original design calculations to determine the effect of this increased packing density on the assumptions made in the design calculations.

Figure 4.16 is an X-ray radiograph of the final assembled canister. The sphere bed nature of the specimen and the relative size of the spheres relative to the total sphere bed dimension can be seen. Because of the small size and brittle nature of the W-Re thermocouple sheath, the alignment of the thermocouples relative to the end caps was critical to ensure that the thermocouple sheaths remained intact during assembly.

4.3 BEATRIX-II, PHASE II IRRADIATION

The Phase II irradiation started May 27, 1992, with the start of FFTF Cycle 12-A.1 and operated for 52.8 EFPD. Cycle 12-A.2 started on July 27, 1992, and operated for 48.6 EFPD. Cycle 12-B.1 started operation on November 21, 1992, with an expected operation time of 50 EFPD. This cycle was still underway at the end of 1991 with an projected shutdown date of mid January 1992. A detailed description of the experimental plan for BEATRIX-II, Phase II from the start until the end of 1991, is given in Appendix B.

4.3.1 Phase II Temperature-Change Canister

The test plan for the temperature-change canister for Cycle 12-A.1 included a series of temperature changes in the three different sweep gases of He, He-0.01% H_2 and He-0.1% H_2 ; and a calibration test series to define the difference in ion chamber response to tritium depending on whether the sweep gas was He or He-0.1% H_2 . Cycle 12-A.2 included a series of temperature changes in He-0.1% H_2 to be used to characterize the effect of burnup, and then a series of gas composition changes were carried out at 645°C. In Cycle 12-B.1 a series of gas composition changes were carried out at 535°C, and then

39103138.5

FIGURE 4.16. X-Ray Radiograph of the Phase II Temperature-Gradient Canister As-Fabricated

a second calibration test series to define the difference in ion chamber response to tritium in He and He-0.1% H_2 , similar to that in Cycle 12-A.1, was repeated.

4.3.1.1 Startup/Temperature Level

An important design objective was to achieve lower temperatures for the Phase II ring specimen than the Phase I Ring specimen. The design temperature for Phase II was 503°C on the inner diameter of the specimen, which is equivalent to an inner thermocouple temperature of 510°C. During startup at a power level of 75% both inner thermocouples were at the same temperature. However, during the final ascent to power a sharp rise in the temperature of one of the thermocouples developed, and a difference in temperature as large as 17°C developed between the thermocouples on either side of the specimen with temperatures of 533 and 550°C at 100% Helium control gas. This temperature difference decreased as the temperature was increased, and with a control gas of 94%Ar-6%He the temperature was reduced to 7°C when the two thermocouples were 644 and 651°C. The reference inner thermocouple temperature was chosen to be $645 \pm 5^\circ\text{C}$.

4.3.1.2 Effect of Sweep Gas Composition on Ion Chamber Response

For the temperature-change canister one of the primary objectives was to obtain definitive data on the behavior of the ion chambers in sweep gases of varying composition. A definitive test was to calibrate an ion chamber in He-0.1% H_2 and in helium. By comparing the results of these calibrations, it is expected that the effect of sweep gas composition of the response of the ion chambers can be determined. These calibrations were carried out in Cycle 12-A.1 and 12-B.1. Unfortunately, the data was not consistent enough to be definitive, so it will be repeated in Cycle 12-B.2.

4.3.1.3 Temperature Transients

Tritium recovery peaks resulting from temperature transients in the Phase II ring specimen for temperature changes between 535 and 645°C were much sharper than observed initially for the Phase I specimen. Figure 4.17 is a series of tritium recovery peaks for a three different temperature transients between 535 and 645°C after 7, 51 and 61 EFPD of irradiation. The Phase I temperature-change canister recovery peaks for temperature transients became progressively sharper with increasing irradiation (see Figure 4.3). Although

92081701.SPS 018/17/92

FIGURE 4.17. Tritium Recovery Following Temperature Transients from 535 to 645°C for the Phase II Temperature-Change Canister at 7, 51 and 61 EFPD

the recovery peaks in Figure 4.17 are over a much shorter irradiation time, there is an indication that a broadening of the recovery peak is occurring.

One proposed explanation for the progressive sharpening of the Phase I tritium recovery peaks for temperature transients was that the phenomenon was not associated with the specimen itself but was related to a drying out of the system. It is noted that similar to the Phase I peak at 295 EFPD the Phase II peaks in Figure 4.17 have no discernable HTO peaks associated with the temperature transient. Figure 4.18 is a direct comparison of the temperature recovery peaks of the Phase I peak at 295 EFPD and the Phase II peak at 7 EFPD. The peaks are plotted as tritium concentration relative to the steady-state recovery rate at the initial temperature prior to the transient. The comparison shows that the recovery peak for the Phase II specimen is sharper and has a greater peak height than the Phase I peak.

Figures 4.19, 4.20 and 4.21 are plots of the recovered tritium concentration for the temperature-change sequence 645-590-535-645°C for the three different sweep gases He-0.1% H_2 , He-0.01% H_2 and He. Similar to the behavior of the Phase I temperature-change canister (Figure 4.1), the recovery peaks for the temperature change of 535 to 645°C are much larger for the sweep gases of He-0.01% H_2 and He relative to the reference sweep gas of He-0.1% H_2 . For decreasing temperatures, the shape of the recovery peaks for He-0.1% H_2 and He-0.01% H_2 are very similar in both size and shape. However, for decreasing temperatures the recovery peaks in helium are larger (more negative) and broader. In fact the peak associated with the change from 590 to 535°C in helium actually rebounds after the decrease to a recovery rate higher than the apparent steady-state recovery rate before or after the temperature change.

4.3.1.4 Temperature/Gas Composition

A series of gas composition changes in the order of He-0.1% H_2 ; 2,4 or 8 days in He; 2 days in He-0.01% H_2 ; and return to He-0.1% H_2 were carried out at 535 and 645°C in Cycles 12-A.2 and 12-B.1 for the Phase II temperature-change canister. In general, the recovery of a steady-state tritium concentration in helium takes considerably longer at 535 than 645°C, suggesting that the tritium inventory increase associated with the change in sweep gas

92081103.SPS 08/12/92

FIGURE 4.18. Comparison of the Tritium Recovery Peaks Associated with a Temperature Change from 550 to 650 of the Phase I Peak at 295 EFPD and the Phase II Peak at 7 EFPD

G0063-C1.SPG 08/11/91

FIGURE 4.19. Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645 $^{\circ}\text{C}$ in a Sweep Gas of He-0.1% H_2 (G0063-01.SPG)

G0064-02.SPG 08/12/91

FIGURE 4.20. Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645°C in a Sweep Gas of He-0.01% H_2 (G0064-02.SPG)

G0065-01.SPG 08/11/91

FIGURE 4.21. Recovered Tritium Concentration for the Phase II Temperature-Control Canister During the Temperature-Change Sequence 645-590-535-645°C in a Sweep Gas of He (G0065-01.SPG)

to helium is much higher at the lower temperature. The transient recovery peaks for gas composition change from He to He-0.01% H_2 and for He-0.01% H_2 to He-0.1% H_2 were both larger for the lower temperature. These larger peaks suggested that gas composition changes at 535°C result in greater inventory changes than the same composition changes at 645°C. This may also be related to the fact that the tritium inventory at 535°C is expected to be larger than at 645°C, for other parameters remaining the same.

4.3.2 Phase II Temperature-Gradient Canister Operation

The test plan for the temperature-gradient specimen for Cycle 12-A.1 included an ion chamber response test to define the ion chamber response to tritium in He sweep gases with additions of H_2 from 0.02% up to 0.5%. These data will be used to make the final decisions on the correction factors to be used converting ion chamber response to tritium concentration. The effect of sweep gas composition on the tritium recovery from the Phase II temperature-gradient canister was studied by a series of tests using He or He-0.01% H_2 for times from 2 to 8 days in Cycles 12-A.1 and 12-A.2. In Cycle 12-B.1, a series of gas composition changes involving both He and He-0.01% H_2 were carried out.

4.3.2.1 Centerline Temperatures

During startup the centerline thermocouples for the solid specimen increased to 1104 and 1060°C for the top and bottom thermocouples at 100% power. The original design calculations had taken into account the expected uncertainties and predicted limits on the centerline temperatures of 1160 to 1030°C (see Table 4.5). The resulting temperatures achieved during the experiment fall in the center of the range.

Figure 4.22 is a plot of the measured centerline temperatures of the Phase II solid specimen for Cycles 12-A.1 and 12-A.2. During a given operating cycle, the centerline temperatures undergo a smooth continual decrease as expected for the decreasing power that occurs through the cycle at the position of the canister. At the start of Cycle 12-B.1 (November 1991) the temperature was found to be nearly equal to the original temperature at start

39208073.3

FIGURE 4.22. Centerline Temperatures for the Operation of the Phase II Temperature-Gradient Canister During FFTF Cycles 12-A.1 and 12-A.2

of cycle 12-A.1 (May 1991) suggesting that most of the decrease in temperatures observed is related to a change in reactor power and not a change in the thermal properties of the sphere bed.

4.3.2.2 Gas Composition Effect

The effect of sweep gas composition on the tritium recovery from the Phase II temperature-gradient canister was studied by a test series using He or He-0.01% H_2 for times from two to eight days in Cycles 12-A.1 and 12-A.2. Helium tests were carried out for durations of two, four, and eight days, while for He-0.01% H_2 testing was carried out for two and four days.

Figure 4.23 is a plot of the recovered tritium concentrations measured during 2-, 4-, and 8-day tests using He sweep gas. The response of the Phase II Li_2ZrO_3 sphere bed specimen to changes in sweep gas is much quicker than the Phase I Li_2O specimen. This response can be compared in Figures 4.8 and 4.9. The change from He-0.1% H_2 to helium results in a sharp decrease in tritium concentration followed by a somewhat slower rise to steady-state in approximately one day. For the Phase I temperature-gradient specimen the achievement of steady state in helium usually required on the order of four days. Likewise, the change in sweep gas composition from helium to He-0.1% H_2 for the Phase II specimen produced a transient peak that was sharper and shorter in duration than seen previously for the Phase I solid.

Although the recovered tritium concentration in Figure 4.23 after approximately one day in helium appears to be at steady-state, successively longer times in helium (two, four and eight days) resulted in a larger tritium recovery peak when the specimen was returned to the reference condition in a sweep gas of He-0.1% H_2 . This suggests that during the apparently flat steady-state period in helium, the specimen is not in equilibrium but is continuing to increase its tritium inventory.

4.3.2.3 Sweep Gas Flow Rate

During the periods when the temperature-change canister ion chamber was being calibrated in helium sweep gas, it was necessary to use the injection gas for a helium purge for establishing background. See for instance PCS #12-19 to 12-21 in Appendix B. Without the availability of a 1% H_2 injection

CO057-01.SPG 08/23/91

FIGURE 4.23. Recovered Tritium Concentrations for the Phase II Temperature-Gradient Canister During 2-, 4- and 8-Day Tests Using He Sweep Gas

gas to add hydrogen to the sweep gas before entering the getter beds, the concentration of hydrogen through the getter beds dropped to 0.05%. Ideally this concentration was maintained at a level of 0.1%. By raising the flow rate of He-0.1% H_2 through the temperature-gradient canister from 100 to 200 ml/min, the H_2 concentration could be raised from 0.05% to 0.067%. Although there were no tritium transient peaks during this period, these lower levels of hydrogen concentration did not appear to affect the operation of the getter beds.

4.4 DATA TRANSFER TO THE MODELERS AND CODE DEVELOPERS

At the March 22, 1991 Working Group Meeting, a decision was made by the BEATRIX-II Working Group to transfer selected sets of BEATRIX-II, Phase I data to Modelers and Code Developers chosen by the individual participants. On September 25 and 26, 1991, an Experimenters Meeting was held to select the data sets and achieve a consensus on procedures to be used in correcting the as-measured data prior to the transfer at the BEATRIX-II Modelers and Code Developers Meeting (MCDM) on November 16, 1991, in Clearwater, Florida. At the Experimenters Meeting it was agreed that the purpose of the MCDM meeting was to provide a uniform "benchmarking" that can be used for validating the various codes from participant countries.

4.4.1 Calibration of BEATRIX-II Ion Chambers in 0.1% H_2 Purge Gas

The first step in achieving a consensus on data reduction parameters was to establish calibration curves for the BEATRIX-II ion chambers in 0.1% H_2 purge gas. The data available to establish such a calibration curve are the initial calibration curves for the ion chambers as supplied by AECL and the analytical results obtained by scintillation analyses of on-line calibration samples taken during the operation of BEATRIX-II.

A comparison of the initial calibration curves for the ion chambers as supplied by AECL and the analytical results obtained by scintillation analyses is given in Table 4.6. The analysis of on-line calibration samples (listed under Analysis) indicated a tritium concentration that was approximately 30% lower than the tritium concentration determined from the ion chamber calibration (listed under Ion Chamber). As an additional check on the analysis of

TABLE 4.6. BEATRIX-II Ion Chamber Calibration - Phase I

Date (d/m/y)	Cycle	Specimen	Location	Flow Rate (mL/min)	Ion Chamber (Ci/m ³)	Analysis (Ci/m ³)	Ratio
2-3-90	11-B.1	Ring	PNL	100	34.6	26.3	1.32
8-10-90	11-B.2	Ring	PNL	100	35.3	27.3	1.29
9-10-90	11-B.2	Ring	PNL	200	17.7	15.6	1.13
			AECL	200	17.7	13.1	1.36
15-3-91	11-C	Ring	PNL	100	34.6	26.6	1.30
4-4-90	11-B.1	Solid	PNL	100	83.2	63.8	1.30
			AECL	100	83.2	58.5	1.42
17-10-90	11-B.2	Solid	PNL	100	86.4	64.9	1.33
			AECL	100	86.4	66.1	1.30
9-3-91	11-C	Solid	PNL	100	86.1	65.1	1.32

the on-line calibration samples, scintillation analyses were carried out both at PNL and AECL. Very good agreement was obtained between the PNL and AECL laboratory measurements of tritium in identical samples.

The proposed solution to the discrepancy between initial ion chamber calibration at AECL and the laboratory analyses of the on-line calibration samples is to use the concentration values determined from the laboratory analyses. This means that the tritium recovery rates indicated by the ionization chambers will be divided by a correction factor to obtain agreement with the laboratory analyses. This correction factor was chosen to be 1.3 based on the values of the ratio between ion chamber and analysis concentrations in Table 4.6.

4.4.2 Ion Chamber Background

It was proposed that the backgrounds on the ionization chambers would be established on the basis of the true tritium concentration T_t as measured by the ion chambers in BEATRIX-II and the apparent tritium concentration T_a as measured in He-0.1% H₂ sweep gas as:

$$T_a = T_t + BG \quad (1)$$

where T_a is the apparent reading, and BG is the background level both for He-0.1% H_2 .

At specific points in Phase I, T_t is determined from the recalibration and clean-gas purges conducted during the Phase I operation. In Phase I this has only been carried out in He-0.1% H_2 . Several times during the steady-state recovery of tritium, a volume of purge gas was collected in a special container and analyzed using scintillation counting. The tritium counted by the analytical laboratory (PNL or AECL) was then available for establishing T_t . The background at the time of the sampling was determined by a clean-gas purge of the ion chamber. Other times during the reactor cycle, when the sweep gas composition is He-0.1% H_2 , T_t is assumed to vary only with reactor power and lithium burnup so that during any steady-state release period, for a given T_a , BG can be readjusted.

4.4.3 Gas Composition Effects

The BEATRIX-II data strongly indicates that the purge gas composition affects the tritium response of the ion chambers. The data also include the following: a dependence of ionization chamber background on sweep gas composition (see Table 4.3); the results of an in situ study on the effects of sweep gas on temperature-gradient canister CEC ionization chamber response carried out in Phase II, Cycle 12-A.1; and general observations made in BEATRIX-II during operation in sweep gases with varying levels of hydrogen. This was discussed previously in Section 4.1.2.3 Tritium Balance Calculations. The initial laboratory calibrations of these ion chambers at AECL in both He and 0.1% H_2 revealed no effect on the ion chamber calibration curve, i.e., current versus tritium concentration.

A more recent evaluation of ion chamber calibration effects is based on the theoretical expression for the ion chamber current, which has the form

$$T_s = K_1 (V_e C g) (FZ) \frac{ef}{W} \quad (2)$$

where I_s is the steady-state ionization current, W is the ionization efficiency of an activated metastable state of helium, and f is the charge

collection efficiency. Because the first ionization potential for H_2 and other impurities is so much lower than for helium, an activated metastable state of He can be produced. For this reason, it is expected that theoretically there should be a dependence of I_s on the gas composition through changes in W . This has been referred to as the Jesse Effect (Hurst and Klots 1976). In recent laboratory experiments with pure helium and 0.1% H_2 , AECL has found that significant changes in ion chamber current could be obtained when very clean, purified gas was flowing through the ion chamber. This was reported at the September 1991 BEATRIX-II Experimenters Meeting.^(a) This relationship explains why the original BEATRIX-II ion chamber calibrations at AECL, which used non-purified sweep gases, indicated that there was no compositional effect in contrast to the results for the same ion chambers which do show a dependence on gas composition under gas flow conditions in FFTF. A phenomenological explanation for this discrepancy is still to be established, but it may be associated with the state of gaseous and surface impurities in the ion chamber. It is proposed that during flowing gas conditions, the impurity levels in the gas are much lower than in the non-flowing case when impurities from the wall can desorb and build up in the gas.

On the basis of the AECL experiments and the BEATRIX-II results it was decided that the following expression would be used to calculate T_t , the true tritium concentration in either pure helium, 0.01% H_2 , or 0.1% H_2 :

$$T_a = \frac{(T_t + BG)}{F} \quad (3)$$

where T_a is the apparent tritium concentration

T_t is the true tritium

BG is background in the respective sweep gas

F is the hydrogen factor.

(a) Hollenberg, G. W. Minutes of BEATRIX-II Experimenters' Meeting, Chalk River Ontario, Canada, September 26-27, 1991. Letter to the BEATRIX-II Working Group, October 10, 1991.

The hydrogen factor F is 1.0 for 0.1% H_2 , 1.25 for 0.01% H_2 , and 1.3 for pure He, according to the observed behavior in BEATRIX-II. It is possible that the F factor may be system-dependent.

A similar type correction for sweep gas composition was used for correcting the tritium recovery results of the temperature-gradient canister in Section 4.1.2.3 Tritium Balance Calculations. However in the correction applied to the temperature-gradient canister in Figures 4.8, 4.9, and 4.10 the correction factors for the particular ion chamber were used as given in Table 4.2. The factors chosen to be used in the data transfer of the temperature-change canister data were taken as an average for all the ion chambers. It is expected that these may be revised in the future.

4.4.4 Data Selection for BEATRIX-II MCDM

The data sets to be distributed at the Modelers and Code Developers Meeting were selected on the basis of several guidelines: 1) the data sets should be representative of the type of behavior observed and should not be abnormal with respect to the entire irradiation test; 2) the temperature-change canister data sets should start at a reference condition and return to the reference condition at the end if possible; 3) the data sets should include time, corrected tritium concentration (CEC side), and temperature, in a LOTUS-type spreadsheet at two-minute intervals; 4) a description of the experiment, including flow rate, temperature gradients, etc., and the specimen; surface area, purity, and grain size, should also be given; and 5) other important qualitative observations should also be including, specifically the observation of moisture peaks associated with the secondary release peaks of tritium on thermal transients, gas composition, effective full power days, calculated tritium generation rate, and relative SPND ratio.

The data sets selected for transfer to MCDM participants are shown in Table 4.7.

TABLE 4.7. Data Sets Transferred to MCDM Participants

Data Set Description	Conditions
1. Temperature Change Sequence	650°C 600°C 550°C 600°C 650°C 550°C 650°C
2. Gas Composition Sequence at 550 and 650°C	Initial/0.1% H ₂ 8 days in He 3 days in 0.01% H ₂ 3 days in 0.1% H ₂
3. Burn-Up Sequence	80 EFPD 210 EFPD 295 EFPD
4. Power Level Sequence During Mid-Cycle	

4.4.5 Data Sets Transferred

Data set #1 included the temperature-change sequence in Cycle 11-B.1 that was carried out during the period from February 21-28, 1990. The temperature changes were conducted in the sequence of 650-600-550-600-650-550-650°C, and the sweep gas composition was He-0.1% H_2 throughout the test sequence. The recovered tritium concentration and inner thermocouple temperature are shown in Figure 4.24. The tritium concentration data are corrected to the sweep gas composition of He-0.1% H_2 and for background as specified by Equation 1. The correlation of thermocouple temperatures to temperatures in the specimen was described as follows:

1. Subtract 6°C from the thermocouple temperature to determine the temperature of the inner surface of the specimen.
2. A listing of the temperature distribution across the thickness of the specimen over the range of inner temperatures was provided. Figure 4.25 illustrates the type of dependence expected.

G0052-01.SPG 10/25/81

FIGURE 4.24. Recovered Tritium Concentration and Inner Thermocouple Temperature for Data Set #1 of the Phase I Temperature-Gradient Canister Transferred at the MCDM

Data Set #2 included two sweep gas composition series of He-0.1% H_2 , eight days in He, three days in He-0.01% H_2 , then finally back to He-0.1% H_2 . The data sets with eight days in helium were chosen over data sets for four days in helium specified by experimenters because of experimental problems that occurred in the available 4-day test series. Figure 4.26 is the recovered tritium concentrations during the sweep gas concentration changes at 650 and 550°C. The series at 650°C was carried out in Cycle 11-B.2 during the period from July 20 to 31, 1990, while the series at 550°C was carried out in Cycle 11-B.2 during the period from September 19 to 30, 1990. In addition to corrections for ion chamber calibration and background, the data have been corrected for sweep gas composition.

Data Set #3 included the temperature-change sequences from 650 to 550 to 650°C that were carried out near the end of each of the three cycles to determine the change in the tritium recovery curves as a result of burnup. Figure 4.27 is a compilation of the three sets of tritium recovery curves produced during the following periods: Cycle 11-B.1 (80 EFPD), April 5 to 7, 1990; Cycle 11-B.2 (215 EFPD), October 23 to 25, 1990, and Cycle 11-C (290 EFPD), March 11 to 13, 1991. The curves have been corrected for ion chamber calibration and background for He-0.1% H_2 sweep gas.

Data Set #4 involved the tritium recovery, inner thermocouple temperature, and relative neutron flux from the self-powered neutron detector (SPND) that was measured before and after an unscheduled reactor shutdown and subsequent startup. Figures 4.28 and 4.29 compare the recovered tritium concentration with the temperature and the relative neutron flux. The shutdown occurred in Cycle 11-B.2 on September 14, 1990, following a problem with a secondary sodium pump. Temperature changes before and after the outage provided additional data for characterizing the specimen behavior during the period. Throughout the period, the sweep gas was He-0.1% H_2 and the corresponding calibration and background corrections were applied to the curves.

39208073.1

FIGURE 4.25. Temperature Distribution Across the Thickness of the Phase I Ring Specimen Over the Range of Inner Temperatures

G0115-01.SPS 08/17/92

FIGURE 4.26. Recovered Tritium Concentrations at 650 and 550°C for Sweep Gas Composition Change Series of $\text{He}-0.1\%\text{H}_2$, 8 Days in He, 3 Days in $\text{He}-0.01\%\text{H}_2$, then Finally Back to $\text{He}-0.1\%\text{H}_2$ for the Phase I Temperature-Change Canister

60066-10.SPS 08/17/92

FIGURE 4.27. Tritium Recovery Curves for Temperature Transients of 650-550-650°C Carried Out During Cycle 11-B.1 (80 EFPD), Cycle 11-B.2(215 EFPD), and Cycle 11-C (290 EFPD) for the Phase I Temperature-Change Canister

CO089-03.SFC 10/30/91

FIGURE 4.28. Recovered Tritium Concentration and Inner Thermocouple Temperature for Data Set #4 Through a Reactor Outage for the Phase I Temperature-Change Canister

20088-02.SPG 10/30/81

FIGURE 4.29. Recovered Tritium Concentration and Relative Neutron Intensity for Data Set #4 Through a Reactor Outage

4.4.6 Data Transfer Participants

The first BEATRIX-II data transfer meeting was held on November 16, 1992, in Clearwater, Florida, in conjunction with the Fifth International Conference on Fusion Materials (ICFRM-5). Representatives from each of the participants were invited and the following is a list of the representatives.

- S. E. Berk, US/DOE
- M. C. Billone, ANL-E
- G. W. Hollenberg, PNL
- C. E. Johnson, ANL-E
- J. P. Kopasz, ANL-E
- J. M. Miller, AECL Research
- K. Noda, JAERI
- H. Moriyama, Kyoto University
- R. Raffrey, UCLA
- O. D. Slagle, PNL
- D. L. Smith, ANL-E
- S. Tanaka, University of Tokyo
- T. Terai, University of Tokyo
- H. Watanabe, JAERI
- M. Yamawaki, University of Tokyo

T. Kurasawa, the JAERI experimenter for BEATRIX-II in-reactor testing, was unable to attend.

4.5 FINAL DATA CORRECTION/COMPILATION

The transfer of BEATRIX-II data at the MCDM required that procedures be determined for correction of the data. One outstanding issue regarding final data analysis is whether or not the correction factors selected for the temperature-change canister data set should be used in the final data correction/compilation.

As described in Section 4.4.3, the effect of sweep gas composition on the response of the ion chambers needs to be determined. A series of on-line ion chamber calibration are being carried out in Phase II to determine the difference in ion chamber response in reference gas He-0.1% H_2 as compared to pure He. It is expected that this series of calibrations will provide a basis for justifying or revising the correction factors used in the final data

analysis. At the conclusion of these recalibrations, the results will be reviewed by the BEATRIX-II experimenters and the best method for analyzing the data will be determined.

Once the analysis procedures are established by the BEATRIX-II experimenters, the procedures and corrected data sets will be published in data analysis reports for Phase I and II.

4.6 TRITIUM PERMEATION EXPERIMENT

A possible uncertainty in the results of both Phase I and II is the loss of tritium from the BEATRIX-II sweep gas system by permeation of tritium through the stainless steel sweep gas tubing and canister walls. In the original design analyses of Phase I (Bauer 1988) tritium losses from permeation through the barrier-coated components were predicted to be low (approximately 1%), but the uncertainty in this analysis remains an issue. It was proposed that an experiment should be carried out to determine the effect of neutron irradiation on the tritium permeation through barrier-coated stainless steel. It was decided that of the options available, the laboratory measurement of tritium permeation on irradiated and versus nonirradiated barrier-coated specimens was the most reasonable choice, considering feasibility and cost.

A matrix of specimens designed to determine the significance of these permeation losses on the measured tritium recovery results was included in BEATRIX-II, Phase II. This matrix of specimens were in the form of discs that can be used as samples for tritium permeation measurements. The matrix of barrier-coated and uncoated specimens of various thicknesses is described in the previous annual report (Slagle and Hollenberg 1991). The specimens were included in the Phase II irradiation in a MOTA-2B level 3 canister expected to achieve, in a 300 EFPD cycle, a nominal fluence equivalent to 30 dpa (in stainless steel) and a below-core canister with a nominal fluence of 5 dpa. A series of unirradiated specimens were also included in the matrix.

It was planned that an experimental system would be set up and used to determine the tritium permeation rate through these disks after irradiation. However because of limited funds, there are presently no plans to carry out these measurements.

4.7 TRITIUM SYSTEMS TEST ASSEMBLY INTERFACE

During 1991, three tritium getter beds were removed from the BEATRIX-II tritium recovery system. This brings the total number of getter beds removed from the BEATRIX-II experiment to seven. At the conclusion of the test, these getter beds will be shipped to LANL for processing and use in the Tritium System Test Assembly (TSTA). Currently, the getter beds are being stored in interim storage at the Hanford Site. The total tritium on each getter bed has been limited to less than 1000 Ci, which classifies them as Type A quantities under U.S. Department of Transportation (DOT) guidelines. Shipments will be limited to one getter bed per shipping container and will be made directly from the FFTF to LANL.

5.0 REFERENCES

- Baker, D. E., T. Kurasawa, J. M. Miller, and O. D. Slagle. 1991. "BEATRIX-II: In Situ Tritium Test Operation." Fusion Technology 19:1640-1645.
- Bauer, R. E. 1988. Test Design Description for the Fusion Materials Open Test Assembly (Fusion MOTA-2A). WHC-SP-0224, Volume 1A, Part 2, Appendix F, November.
- Billone, M. C., C. C. Lin, H. Attaya, and Y. Gohar. 1991. "Tritium Retention and Release Analysis for the U.S.-ITER Blanket." Fusion Technology 19:976-983.
- Briec, M., J. J. Abassin, C. E. Johnson, M. Amasson, N. Roux and H. Watanabe. September 19-23, 1988. "The MOZART Experiment: In-Pile Tritium Extraction from Lithium Oxide, Aluminates' Zirconates." In Proceedings of the 15th Symposium on Fusion Technology, A. M. Van Inger, A. Nigsen-Vis, and H. P. Kippel eds, pp 1105-1111. Utrecht, The Netherlands. Elsevier, Netherlands.
- Clemmer, R. G., et al. 1984. "The TRIO-1 Experiment: In-Situ Tritium Recovery Results." J. Nucl. Mater. 122-123, 80.
- Hollenberg, G. W. 1989. First Annual Progress Report, BEATRIX-II Program - January 1988 to December 1988. PNL-6818. Pacific Northwest Laboratory, Richland, Washington.
- Hollenberg, G. W., and D. L. Baldwin. 1985. "The Effect of Irradiation on Four Solid Breeder Materials." J. Nucl. Mater. 133 & 134, 242-245.
- Hollenberg, G. W., T. Kurasawa, S. E. Berk, I. J. Hastings, and D. E. Baker. 1989. "A Fast Neutron, In situ Tritium Recovery Experiment on Solid Breeder Materials." Fusion Technology 15:1349-1354.
- Hurst, G. S. and C. E. Klotz. 1976. Advances in Radiation Chemistry, M. Burton and J. L. Magee eds. Vol. 14, John Wiley and Sons, New York.
- Konishi, S., H. Yoshida, H. Ohno, Y. Naruse, D. O. Coffin, C. R. Walthers, and K. E. Binning. 1987. "Experiments on a Ceramic Electrolysis Cell and a Palladium Diffuser at the Tritium Systems Test Assembly." Fusion Technology 8:2042-2047.
- Kurasawa, T., et al. 1986. "The Time Dependence of In-Situ Tritium Release from Lithium Oxide and Lithium Aluminate (VOM-22H Experiment)." J. Nucl. Mater. 141-143, 265.
- Kurasawa, T., O. D. Slagle, G. W. Hollenberg, and R. A. Verrall. 1991. "Insitu Tritium Recovery from Li_2O Irradiated in Fast Neutron - BEATRIX-II: In Situ Tritium Test Operation." Fusion Technology 19:931-937.

Norman, J. H., and G. R. Hightower. 1984. J. Nucl. Mater. 122 & 123 (1984) 913.

Puigh, R. J., G. W. Hollenberg, T. Kurasawa, H. Watanabe, I. J. Hastings, J. M. Miller, S. E. Berk, R. E. Bauer, and D. E. Baker. September 19-23, 1988. "BEATRIX-II: In Situ Tritium Recovery from a Fast Neutron Irradiation Of Solid Breeder Materials." In Proceedings of the 15th Symposium on Fusion Technology, A. M. Van Inger, A. Nigsen-Vis, and H. P. Kippel eds, pp 1282-1286. Utrecht, The Netherlands, Elsevier, Netherlands.

Slagle, O. D., and G. W. Hollenberg. 1990a. "Irradiation Performance of Li_2O and LiAlO_2 Under Large Temperature Gradients." In Fabrication and Properties of Lithium Ceramics II: Advances in Ceramics, Vol. 27, G. W. Hollenberg and I. J. Hastings eds. The American Ceramic Society, Westerville, Ohio.

Slagle, O. D., and G. W. Hollenberg. 1990b. Second Annual Progress Report, BEATRIX-II Program - January 1989 to December 1989. PNL-7477, Pacific Northwest Laboratory, Richland, Washington.

Slagle, O. D., and G. W. Hollenberg. 1991. Third Annual Progress Report, BEATRIX-II Program - January 1990 to December 1990. PNL-7858, Pacific Northwest Laboratory, Richland, Washington.

Slagle, O. D., G. W. Hollenberg, and D. L. Baldwin. 1991. "The FUBR-1B Experiment - Tritium Release and Physical Stability of Solid Breeder Materials." J. Nucl. Mater. 179-181, 843-846.

Slagle, O. D., T. Kurasawa, R. A. Verrall, and G. W. Hollenberg. 1991. "In-situ Tritium Recovery from Li_2O Irradiated in Fast Neutron Flux--BEATRIX-II Temperature Change Specimen."² PNL-SA-19283 presented at ICFRM-5 in Clearwater, Florida on November 17-22, 1991.

Tetenbaum, M., and C. E. Johnson. 1984. J. Nucl. Mater. 126 (1984) 25.

Verrall, R. A., J. M. Miller, D. S. MacDonald, and S. R. Bokwa. 1988. "CRITIC-1 Irradiation of Lithium Oxide." J. Nucl. Mater. 155-157, 553-557.

APPENDIX A

EXPERIMENTER'S LOG FOR BEATRIX-II, PHASE I IN FFTF CYCLE 11-C

EXPERIMENTER LOG - Cycle 11-C

PCS No.	Date	Ring Specimen				Solid Specimen				Remarks
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		Flow Rate/Gas Comp		
Initial	Final	Initial	Final	Initial	Final	Initial	Final			
Reactor Startup 12-21-90 at 000 hrs										
11-132	12-28-90	553		He	0.1 H ₂	He	0.01 H ₂	T(min)=553°C		
11-133	12-30-90	553	650	0.1 H ₂		0.01 H ₂	0.1 H ₂			
11-134	1-2-91	650	550	0.1 H ₂		0.1 H ₂				
11-135	1-3-91	550	650	0.1 H ₂		0.1 H ₂				
11-136	1-4-91	650	600	0.1 H ₂		0.1 H ₂	He	Reactor Power Changed		
11-137	1-5-91	600	650	0.1 H ₂		He				
11-138	1-6-91	650	600	0.1 H ₂		He				
11-139	1-7-91	600	550	0.1 H ₂		He		T(min)=556°C		
11-140	1-8-91	550	600	0.1 H ₂		He	0.01 H ₂	T ₀ = 9:32		
11-141	1-9-91	600	650	0.1 H ₂		0.01 H ₂				
11-142	1-10-91	650		0.1 H ₂	0.01 H ₂	0.01 H ₂				
11-143	1-11-91	650	550	0.01 H ₂		0.01 H ₂				
11-144	1-12-91	550	650	0.01 H ₂		0.01 H ₂				
11-145	1-13-91	650		0.01 H ₂	0.1 H ₂	0.01 H ₂				
11-146	1-14-91	650		0.1 H ₂	0.01 H ₂	0.01 H ₂	0.1 H ₂			
11-147	1-15-91	650	600	0.01 H ₂		0.1 H ₂				

PCS No.	Date	Ring Specimen			Solid Specimen			Remarks
		Temperature		Flow Rate/Gas Comp	Flow Rate/Gas Comp			
		Initial	Final		Initial	Final		
11-148	1-16-91	600	550	0.01 H ₂		0.1 H ₂		
11-149	1-17-91	550	600	0.01 H ₂		0.1 H ₂		
11-150	1-18-91	600	650	0.01 H ₂		0.1 H ₂		
11-151	1-19-91	650		0.01 H ₂	0.1 H ₂	0.1 H ₂		
Getter Zed Changeout on 1-21-91								
11-152	1-21-91	650		0.1 H ₂	He	0.1 H ₂		
11-153	1-23-91	650	550		He	0.1 H ₂		
11-154	1-25-91	550	650		He	0.1 H ₂		
11-155	1-27-91	650		He	0.1 H ₂	0.1 H ₂		
11-156	1-29-91	650		0.1 H ₂	He	0.1 H ₂		
11-157	1-31-91	650	600	He		0.1 H ₂	He	
11-158	2-2-91	600	550	He		He		
11-159	2-4-91	550	600	He		He		
11-160	2-6-91	600	650	He		He		
11-161	2-8-91	650		He	0.01 H ₂	He	0.01 H ₂	
11-162	2-10-91	650		0.01 H ₂	0.1 H ₂	0.01 H ₂		
Unscheduled reactor shutdown at 1100 hrs February 11, 1991								
11-163	2-12-91	650	550	0.1 H ₂		0.01 H ₂	0.1 H ₂	Reactor shutdown
11-164	2-15-91	550	650	0.1 H ₂		0.1 H ₂		

PCS No.	Date	Ring Specimen				Solid Specimen			Remarks	
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		Initial		Final
		Initial	Final	Initial	Final	Initial	Final	Initial		Final
11-165	2-17-91	650		0.1 H ₂	0.01 H ₂					
11-166	2-19-91	650		0.01 H ₂	He					
11-167	2-23-91	650		He	0.1 H ₂					
11-168	2-24-91	650	550	0.1 H ₂						
11-169	2-26-91	550		0.1 H ₂	0.01 H ₂					
11-170	2-28-91	550		0.01 H ₂	He					
11-171	3-1-91	Change high alarm limits for CEC cell								
11-172	3-4-91	550		He	0.1 H ₂					
11-173	3-5-91	550		0.1 H ₂		0.1 H ₂	1.0 H ₂			
11-174	3-6-91	650		0.1 H ₂		1.0 H ₂	0.1 H ₂			
11-175	3-8-91	650	600	0.1 H ₂		0.1 H ₂		Purge RE-52271-1		
11-176	3-9-91	600	550	0.1 H ₂		0.1 H ₂		Calibrate RE-52271-1		
11-177	3-10-91	550	650	0.1 H ₂		0.1 H ₂		Purge RE-52271-1		
11-178	3-11-91	650	550	0.1 H ₂		0.1 H ₂		Stop Purge		
11-179	3-12-91	550	650	0.1 H ₂		0.1 H ₂				
11-180	3-13-91	650		0.1 H ₂		0.1 H ₂		Purge RE-52270-1		
11-181	3-15-91	650		0.1 H ₂		0.1 H ₂		Calibrate RE-52270-1		
11-182	3-16-91	650		0.1 H ₂		0.1 H ₂		Purge RE-52270-2		
11-183	3-17-91	650		0.1 H ₂		0.1 H ₂		Purge Re-52270-1		

PCS No.	Date	Ring Specimen				Solid Specimen		Remarks
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		
		Initial	Final	Initial	Final	Initial	Final	
11-184	3-18-91	650		0.1 H ₂		0.1 H ₂		Purge RE-52271-1
11-185	3-20-91	650		0.1 H ₂		0.1 H ₂		Stop Purge
	3-20-91	Reactor shutdown at end of Cycle 11-C.						
11-186	3-21-91	Change in specified alarm limits.						
11-187	3-25-91	NA		0.1 H ₂	He	0.1 H ₂	He	
11-188	3-26-91	NA		He	0.01 H ₂	He	0.01 H ₂	
11-189	3-27-91	NA		0.01 H ₂	0.1 H ₂	0.01 H ₂	0.1 H ₂	
11-190	3-28-91	NA		0.1 H ₂	He	0.1 H ₂	He	

APPENDIX B

EXPERIMENTER'S LOG FOR BEATRIX-II, PHASE II
IN FFTF CYCLES 12-A AND 12-B IN CY 1991

EXPERIMENTER LOG - Cycle 12-A

PCS No	Date	Ring Specimen		Solid Specimen		Remarks
		Temperature		Flow Rate/Gas Comp		
		Initial	Final	Initial	Final	
12-1	5-11-91			He	He	Parameter Adjustment
12-2	5-14-91			He	He purge of CEC	Purge Purge RE-52771
12-3	5-15-91			He	Secure Purge	
12-4	5-18-91	He Purge of CEC-IC		He		Purge RE-52270-1
12-5	5-19-91	Secure Purge		He	He purge of CEC	
12-6	5-20-91			He	Secure Purge	
12-7				He	0.1 H ₂	
Reactor startup on May 27, 1991						
12-8	5-29-91			Increase CEC volts	0.1 H ₂	
12-9	5-31-91	100 to 75% He		0.1 H ₂	0.1 H ₂	
12-10	5-31-91	75% to 10% He		0.1 H ₂	0.1 H ₂	
12-11	6-2-91	645	590	0.1 H ₂	0.1 H ₂	
12-12	6-3-91	590	535	0.1 H ₂	0.1 H ₂	
12-13	6-4-91	535	645	0.1 H ₂	0.1 H ₂	
12-14	6-6-91	645		Purge CEC IC - 0.1	0.1 H ₂	Purge RE-52270-1
12-15	6-7-91	645		Take Calib Sample	0.1 H ₂	CEC Cell Failed
12-16	6-8-91	645		Purge CEC IC - 0.1	0.1 H ₂	

PCS No	Date	Ring Specimen				Solid Specimen			Remarks	
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		Initial		Final
		Initial	Final	Initial	Final	Initial	Final	Initial		Final
12-17	6-10-91	645		Take Calib Sample		0.1 H ₂		t=16:58		
12-18	6-10-91	645		0.1 H ₂	He	100	200			
12-19	6-12-91	645		Purge CEC IC - He		200				
12-20	6-13-91	645		Take Calib Sample		200		t=14:53		
12-21	6-14-91	645		He	0.1 H ₂	200	100			
12-22	6-17-91	590		0.1 H ₂		0.1 H ₂	He			
12-23	6-18-91	535		0.1 H ₂		He		50 mL He		
12-24	6-19-91	535		0.1 H ₂		He		50 mL He + 3 mL 1% H ₂		
12-25	6-19-91	535		0.1 H ₂		He		50 mL He + 6 mL 1% H ₂		
12-26	6-19-91	535		0.1 H ₂		He		50 mL He + 13 mL 1% H ₂		
12-27	6-19-91	535		0.1 H ₂		He		50 mL He + 50 mL 1% H ₂		
12-28	6-19-91	535	645	0.1 H ₂		He		50 mL He		
12-29	6-21-91	645		0.1 H ₂	0.01 H ₂	He	0.01 H ₂			
12-30	6-23-91	645		0.01 H ₂		0.01 H ₂	0.1 H ₂			
12-31	6-24-91	645	590	0.01 H ₂		0.1 H ₂				
12-32	6-26-91	590	535	0.01 H ₂		0.1 H ₂				
12-33	6-28-91	535	645	0.01 H ₂		0.1 H ₂				
12-34	6-30-91	645		0.01 H ₂	0.1 H ₂	0.1 H ₂	0.01 H ₂			
12-35	7-2-91	645		0.1 H ₂	He	0.01 H ₂	0.1 H ₂			

PCS No	Date	Ring Specimen			Solid Specimen			Remarks
		Temperature		Flow Rate/Gas Comp	Flow Rate/Gas Comp			
		Initial	Final		Initial	Final		
12-36	7-6-91	645	590	He		0.1 H ₂		
12-37	7-8-91	590	535	He		0.1 H ₂		
12-38	7-9-91	535		He		0.1 H ₂	He	
12-39	7-10-91	535	645	He		He		
12-40	7-11-91	645		He		He	0.1 H ₂	
12-41	7-12-91	645		He	0.01 H ₂	0.1 H ₂		t ₀ =10:47
12-42	7-14-91	645		0.01 H ₂	0.1 H ₂	0.1 H ₂		
12-43	7-16-91	645	590	0.1 H ₂				
12-44	7-17-91	590	528	0.1 H ₂				
12-45	7-18-91	528	645	0.1 H ₂				
End of Cycle 12-A.1; Reactor shutdown on July 20, 1991								
12-46	7-22-91	N/A		0.1 H ₂	He	0.1 H ₂	He	
12-47	7-23-91			He		Purge #9, 1% H ₂		0.057% H ₂
12-48	7-24-91			He				0.107% H ₂
12-49	7-25-91			He				0.5% H ₂
12-50	7-25-91			He				0.206% H ₂
12-51	7-26-91			He				0.107% H ₂
12-52	7-26-91			He				0.057% H ₂
12-53	7-27-91			He		Purge Stopped		

PCS No	Date	Ring Specimen				Solid Specimen		Remarks
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		
		Initial	Final	Initial	Final	Initial	Final	
12-54	7-29-91	100% Helium		He	0.1 H ₂	He	0.1 H ₂	
Start of Cycle 12-A.2: July 30, 1991								
12-55	8-5-91	530	645	0.1 H ₂		0.1 H ₂		Temperature adjustment
12-56	8-6-91	645	645	0.1 H ₂		0.1 H ₂		
12-57	8-7-91	645	590	0.1 H ₂		0.1 H ₂		
12-58	8-8-91	590	530	0.1 H ₂		0.1 H ₂		
12-59	8-9-91	530	645	0.1 H ₂		0.1 H ₂		
12-60	8-10-91	645	530	0.1 H ₂		0.1 H ₂		
12-61	8-11-91	530	645	0.1 H ₂		0.1 H ₂		
12-62	8-13-91	645		0.1 H ₂	He	0.1 H ₂		
12-63	8-15-91	645		He	0.01 H ₂	0.1 H ₂	0.01 H ₂	t ₀ R=11:35, t ₀ S=13:08
12-64	8-17-91	645		0.01 H ₂	0.1 H ₂	0.01 H ₂		
12-65	8-19-91	645		0.1 H ₂		0.01 H ₂	0.1 H ₂	
Getter Bed XX-52280-2 Changeout								
12-66	8-21-91	645		0.1 H ₂	He	0.1 H ₂	He	
12-67	8-25-91	645		He	0.01 H ₂	He	0.1 H ₂	
12-68	8-27-91	645		0.01 H ₂	0.1 H ₂	0.1 H ₂		146 Ci/m ³
12-69	8-28-91	645		0.1 H ₂		0.1 H ₂	He	
12-70	8-31-91	645		0.1 H ₂	He	He		

PCS No	Date	Ring Specimen				Solid Specimen		Remarks
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		
		Initial	Final	Initial	Final	Initial	Final	
12-71	9-5-91	645		He		He	0.1 H ₂	187 Ci/m ³
12-72	9-8-91	645		He	0.01 H ₂	0.1 H ₂		t ₀ R=9:46
12-73	9-9-91	645		0.01 H ₂		25 CEC : 75 MS		Flow Rate Test
12-74	9-10-91	645		0.01 H ₂	0.1 H ₂	25 CEC : 75 MS		
12-75	9-11-91	645		0.1 H ₂		50 CEC : 50 MS		
12-76	9-12-91	645		0.1 H ₂		0.1 H ₂		Purge RE-52270-1
12-77	9-13-91	645		0.1 H ₂		50 IG to CEC IC		Calibrate RE-52270-1
12-78	9-14-91	645		0.1 H ₂		0.1 H ₂		Purge RE-52270-2
12-79	9-15-91	645		0.1 H ₂		0.1 H ₂		Calibrate RE-52270-2
12-80	9-16-91	645		0.1 H ₂		Purge CEC IC		
12-81	9-17-91	645		0.1 H ₂		Purge MS IC		
12-82	9-18-91	645		0.1 H ₂		0.1 H ₂		Secure Purges
12-83	9-19-91	645		0.1 H ₂	He	0.1 H ₂	He	
Reactor Shutdown on 9-21-91								
12-84	9-22-91	N/A		He	0.01 H ₂	He	0.01 H ₂	
12-85	9-23-91	N/A		0.01 H ₂	0.1 H ₂	0.01 H ₂	0.1 H ₂	
12-86	9-24-91	N/A		0.1 H ₂	He	0.1 H ₂	He	CEC voltage to -0.9 V
12-87	9-25-91	N/A		He	0.1 H ₂	He	0.1 H ₂	
12-88	10-15-91			He		0.1 H ₂	He	

PCS No	Date	Ring Specimen				Solid Specimen				Remarks
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		Initial	Final	
		Initial	Final	Initial	Final	Initial	Final			
12-89	10-17-91					He		He @ 100 ml/min		Purge RE-52271-1(He)
12-90	10-18-91					He		He @ 50 ml/min		Stop Purge
12-91	10-21-91					He		He	0.1 H ₂	
12-92	10-22-91					He		0.1 H ₂	He	Purge RE-52271-1(0.1 H ₂)
12-93	10-23-91					He		He		Purge RE-52271-2(0.1 H ₂)
12-94	10-24-91					He		He		Stop Purge
12-95	10-28-91					He	0.1 H ₂	He		
12-96	10-29-91					0.1 H ₂	He	He		Purge RE-52270-1(0.1 H ₂)
12-97	10-30-91					He		He		Purge RE-52270-2(0.1 H ₂)
12-98	10-31-91									Stop Purge
12-99	11-15-91	Injection gas changed to 1.0% H ₂								
Start of Cycle 12-B.1: November 21, 1991										
12-100	11-22-91	Voltage for electrolysis cell increased for restart								
12-101	11-26-91	480	580	He		He				Reactor Power @ 75%
12-102	11-27-91	630	525	He		He				Reactor Power @ 90%
12-103	11-29-91	535	645	He		He		He	0.1 H ₂	
12-104	11-30-91	645		He	0.1 H ₂	0.1 H ₂				

PCS No	Date	Ring Specimen				Solid Specimen				Remarks	
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp		Flow Rate/Gas Comp			
12-105	12-2-91	Gas bottle changed for upcoming purge									
On December 2, 1991 the instrumentation lost power at 9:00 - Data interruption expected											
12-106	12-3-91	645			0.1 H ₂			0.1 H ₂		Purge RE-52270-1(0.1% H ₂)	
12-107	12-4-91	645			0.1 H ₂			0.1 H ₂		Gas Sample XN-7-2	
12-108	12-5-91	645			0.1 H ₂	He		200 ml/min			
12-109	12-7-91	645			He			200 ml/min		Purge RE-52270-1(He)	
12-110	12-8-91	645			He			200 ml/min		Gas Sample XN-7-2	
12-111	12-9-91	645			He	0.1 H ₂		0.1 H ₂			
12-112	12-11-91	645	535		0.1 H ₂			0.1 H ₂			
12-113	12-12-91	535			0.1 H ₂	He		0.1 H ₂	He		
12-114	12-14-91	535			He	0.01 H ₂		He	0.01 H ₂		
12-115	12-16-91	535			0.01 H ₂	0.1 H ₂		0.01 H ₂	0.1 H ₂		
12-116	12-17-91	535	Remove calibration sample taken during PCS 12-110								
12-117	12-18-91	535			0.1 H ₂	He		0.1 H ₂	He		
12-118	12-22-91	535			He	0.01 H ₂		He	0.01 H ₂		
12-119	12-24-91	535			0.01 H ₂	0.1 H ₂		0.01 H ₂	0.1 H ₂		
12-120	12-27-91	535			0.1 H ₂	0.01 H ₂		0.1 H ₂	0.01 H ₂		
12-121	12-29-91	535			0.01 H ₂	He		0.01 H ₂	He		

PCS No	Date	Ring Specimen				Solid Specimen			Remarks	
		Temperature		Flow Rate/Gas Comp		Flow Rate/Gas Comp				
				Initial	Final	Initial	Final			
				Initial	Final	Initial	Final	Initial		Final
12-122	12-31-91			535		He		He	0.1 H ₂	
12-123	1-2-92			535		He	0.1 H ₂	0.1 H ₂		

APPENDIX C

1991 PUBLICATIONS AND PRESENTATIONS

APPENDIX C

1991 PUBLICATIONS AND PRESENTATIONS

PUBLICATIONS

O. D. Slagle and G. W. Hollenberg, Third Annual Progress Report, BEATRIX-II Program - January 1990 to December 1990. October 1991, PNL-7858.

D. E. Baker, T. Kurasawa, J. M. Miller, and O. D. Slagle, "Beatrix-II: In-Situ Tritium Test Operation," Fusion Technology 19, 1991, 1640-1645, PNL-SA-18617.

T. Kurasawa, O. D. Slagle, G. W. Hollenberg, and R. A. Verrall, "In-Situ Tritium Recovery from Li_2O Irradiated in Fast Neutron Flux - BEATRIX-II Initial Results," Fusion Technology 19, 1991, 931-937, PNL-SA-18619.

O. D. Slagle, G. W. Hollenberg, and D. L. Baldwin, "The FUBR-1B Irradiation Experiment - Tritium Release and Physical Stability of Solid Breeder Materials," Journal of Nuclear Material 179-181, 1991, 843-846, PNL-SA-16939.

PRESENTATIONS

The following two papers were presented at the American Ceramic Society Meeting in Cincinnati, Ohio on May 29 to June 2, 1991:

- O. D. Slagle, T. Takahashi (JAERI), J. D. Sullivan (AECL), and R. C. Knight (WHC), "Irradiation Experiment Design for In Situ Tritium Recovery for Li_2O and Li_2ZrO_3 - BEATRIX-II, Phase II," PNL-SA-19030.
- T. Kurasawa (JAERI), O. D. Slagle, G. W. Hollenberg and R. A. Verrall (AECL), "In Situ Tritium Recovery from Li_2O Irradiated under a Large Temperature Gradient - BEATRIX-II Solid Specimen", PNL-SA-19029.

The following papers were presented at ICFRM-5 in Clearwater, Florida on November 17 to 22, 1991:

- G. W. Hollenberg, H. Watanabe, I. J. Hastings, and S. E. Berk, "BEATRIX-II: A Multi-National Solid Breeder Experiment," PNL-SA-20123.
- O. D. Slagle, T. Kurasawa, R. A. Verrall, and G. W. Hollenberg, "In-situ Tritium Recovery from Li_2O Irradiated in Fast Neutron Flux - BEATRIX-II Temperature Change Specimen," PNL-SA-19283.

The following paper was presented at the Second Workshop on Solid Breeder Interactions in Clearwater, Florida on November 22 and 23, 1991:

- O. D. Slagle, and T. Kurasawa, "In-situ Tritium Recovery from Li_2O Irradiated in Fast Neutron Flux - BEATRIX-II: Effect of Sweep Gas Composition," PNL-SA-20188.

DISTRIBUTION

No. of
Copies

No. of
Copies

OFFSITE

12 DOE/Office of Scientific and
Technical Information

3 ER-533, GTN
U.S. Department of Energy
Office of Fusion Energy
Washington, DC 20545
ATTN: S. E. Berk
R. E. Price
F. W. Wiffen

N. A. Davies
Tokamak System Branch
Division of Magnetic Fusion
Energy
U.S. Department of Energy
Washington, DC 20545

M. Roberts
Project Office
ER-521, GTN
U.S. Department of Energy
Office of Fusion Energy
Washington, DC 20545

2 Los Alamos National Laboratory
Mail Stop C3-48
Los Alamos, NM 87545
ATTN: J. L. Anderson
J. L. Bartlit

C. Baker
Los Alamos National Laboratory
P.O. Box 1663
Los Alamos, NM 87545

C. C. Baker
Oak Ridge National Laboratory
P.O. Box 2009
Oak Ridge, TN 37831

C. G. Bathke
Los Alamos National Laboratory
P.O. Box 1663
Mail Stop H821
Los Alamos, NM 87545

3 Argonne National Laboratory
9700 South Cass Avenue
Building 205
Argonne, IL 60439
ATTN: M. Billone
Y. Gohar
C. E. Johnson

J. P. Kopasz
Argonne National Laboratory
9700 South Cass Ave.
Argonne, IL 60439

D. L. Smith
Fusion Power Program
Argonne National Laboratory
9700 South Cass Avenue
Building 205
Argonne, IL 60439

3 EG&G
P.O. Box 1625
Idaho Falls, ID 83415
ATTN: S. Piet
P. Lessing
R. Marshall

K. Schultz
General Atomic
P.O. Box 81608
San Diego, CA 92138

R. Moir
Lawrence Livermore National
Laboratories
P.O. Box 5511 L-644
7000 East Avenue
Livermore, CA 94550

No. of
Copies

- 2 School of Engineering and
Applied Science
UCLA
Boelter Hall
405 Hilgard Avenue
Los Angeles, CA 90024
ATTN: M. Abdou
R. Raffray

FOREIGN

- 6 Atomic Energy of Canada Ltd.
Research Company
Chalk River Nuclear Laboratory
Chalk River, Ontario
CANADA KOJ 1J0
ATTN: R. E. Green
D. P. Jackson
J. M. Miller
R. A. Verrall
E. O. Moeck
H. K. Rae
- 3 I. J. Hastings
Atomic Energy of Canada Ltd.
344 Slater Street
Ottawa, Ontario
CANADA KJA OJ4
- G. J. Phillips
Fusion Fuels
Fusion Canada
Atomic Energy of Canada Ltd.
Research Company
Chalk River Nuclear Laboratory
Chalk River, Ontario
CANADA KOJ 1J0
- 3 Canadian Fusion Fuels
Technology Project
2700 Lakeshore Road West
MISSISSAUGA
Ontario L5J 1K3
CANADA
ATTN: D. P. Dautovich
P. Gierszewski
K. Wong

No. of
Copies

- J. Darvas
DG XII - Fusion, SdM
200, rue de la Loi
B 1040 Brussels
BELGIUM
- 23 Department of Fuels and
Materials Research
Japan Atomic Energy Research
Institute
Tokai-mura Naka-gun
Ibaraki-ken 319-11
JAPAN
ATTN: T. Kondo
T. Kurasawa
Y. Naruse
K. Noda (20)
- H. Yoshida
Department of ITER Project
801-1, Mukouyama, Naka-machi,
Naka-gun
Ibaraki-ken, 311-01
JAPAN
- H. Moriyama
Department of Nuclear
Engineering
Kyoto University
Yoshida, Sakyo-ku
Kyoto 606-01
JAPAN
- T. Terai
Department of Nuclear
Engineering
University of Tokyo
Hongo, Bunkyo-ku
Tokyo 7-3-1
JAPAN
- M. Yamawaki
Department of Nuclear
Engineering
Faculty of Engineering
University of Tokyo
7-3-1 Hongo, Bunkyo-ku, Tokyo
JAPAN

No. of
Copies

S. Tanaka
Nuclear Engineering Research
Laboratory
University of Tokyo
2-22 Shirakata-Shirane
Tokai-mura, Naka-gun
Ibaraki-ken 319-11
JAPAN

ONSITE

2 DOE Richland Field Office

D. R. Segna, A5-90
B. A. Hays, A3-55

No. of
Copies

9 Westinghouse Hanford Company

D. E. Baker, L6-39
R. E. Bauer, L6-37
K. R. Birney, L6-36
D. S. Dutt, L5-60
H. W. Heacock, H0-30
J. J. Holmes, L5-55
R. C. Knight, L6-37
R. J. Puigh, L6-39
H. H. Yoshikawa, B1-31

43 Pacific Northwest Laboratory

D. L. Baldwin, P7-22
R. G. Clemmer, P7-18
J. L. Ethridge, P8-34
M. D. Freshley, P8-10
G. W. Hollenberg, P8-10 (10)
R. H. Jones, P8-15
B. D. Shipp, K1-73
O. D. Slagle, P8-10 (20)
G. L. Tingey, P8-10
Publishing Coordination
Technical Report Files (5)

END

**DATE
FILMED**

3 / 10 / 93