HOT GAS DESULFURIZATION WITH SORBENTS
CONTAINING OXIDES OF ZINC, IRON, VANADIUM AND COPPER

GRANT NUMBER: DE-FG22-90PC90312
START DATE: October 1, 1990
EXPECTED COMPLETION DATE: December 31, 1992

PRINCIPAL INVESTIGATOR: Ates Akyurtlu
CO-INVESTIGATOR: Jale F. Akyurtlu

Department of Engineering
Hampton University
Hampton, VA 23668

Quarterly Technical
Progress Report
July 1992

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

JUL 27 1992

ABSTRACT

The main objective of this research is to evaluate the desulfurization performance of novel sorbents consisting of different combinations of zinc, iron, vanadium and copper oxides; and to develop a sorbent which can reduce H_2S levels to less than 1 ppmv, which can stabilize zinc, making operations above $650^{\circ}C$ possible, and which can produce economically recoverable amounts of elemental sulfur during regeneration. This objective will be accomplished by evaluating the sorbent performance using fixed-bed and TGA experiments supported by sorbent characterization at various reaction extents.

In the seventh quarter, the screening of the promoted sorbents in the packed bed reactor was continued.

The results of this work were presented at the 1992 University Coal Research Contractors' Review Conference at Pittsburgh, PA.

WORK DONE

The results from this work were presented at the 1992 University Coal Research Contractors' Review Conference in Pittsburgh, PA. Since the presentation summarizes all the results obtained to date, it will be enclosed as follows to cover the sections 'Work Done' and 'Results' in this report.

OBJECTIVE

To develop a new high temperature fuel gas desulfurization sorbent which can lower H_2S concentrations to below 2 ppmv, stabilize zinc at high temperatures, suppress sulfate formation during regeneration, produce economically recoverable amounts of elemental sulfur, and possess reasonable sulfur capacity.

POWER GENERATION SYSTEMS

- **Integrated Gasification Combined Cycle (IGCC)**

Sulfur level < 10 ppm to reduce turbine blade corrosion.

- **Molten Carbonate Fuel Cells (MCFC)**

Sulfur level < 1 ppm to prevent poisoning of cell electrodes.

Process Economics :

800-1100 K

IMPORTANT DESULFURIZATION SORBENT PROPERTIES

- H_2S removal efficiency
- Sulfur capture capacity
- Regenerability over multiple cycles
- Composition of the regeneration off-gas
- Durability of physical strength
- Behavior towards other impurities

ZINC FERRITE SORBENTS

REACTIONS

Reduction:

Sulfidation:

Regeneration:

ZINC FERRITE SORBENTS

LIMITATIONS

- Sulfidation temperature limited by evaporative loss of zinc.
- Regeneration temperature limited by sulfate formation and surface area loss.
- Prebreakthrough H_2S levels.

ADVANTAGES OF ZINC TITANATE SORBENTS

- ZnO is stabilized against reduction.
- Sub-equilibrium H_2S levels are obtained.
- Sulfate formation is suppressed.

DISADVANTAGE OF ZINC TITANATE SORBENT

- Low sulfur capture capacity.

V_2O_5 AS A DESULFURIZATION SORBENT

Error in the calculation of heat of formation of V_2S_3
-227 kcal/mole vs -125 kcal/mole

- Sulfidation equilibrium is inferior to that of zinc.
- Sulfidation kinetics is an order of magnitude slower than that of ZnO.

PERFORMANCE OF SUPPORTED $\text{ZnO-V}_2\text{O}_5$

- Stable breakthrough conversion of about 0.65 over 6 cycles (sulfur loading=0.0027 g S/g sorbent).
- Prebreakthrough H_2S levels less than 1 ppmv.
- Stabilization of ZnO against reduction.
- Significant H_2S chemisorption.
- Regeneration at high temperatures without surface area loss.
- Significant amounts of elemental sulfur formation during dry regeneration.
- No sulfate formation.

$\text{Zn/V}_2\text{O}_5$ eutectic:

Mole ratio= 0.98/1

Fusion temperature= 661°C

ZnO-V₂O₅ SORBENTS

REACTIONS

Sulfidation:

Regeneration:

WHY ZINC FERRITE - VANADIUM OXIDE MIXTURES?

- To increase sorbent capacity
- Iron oxide seems to be necessary for production of elemental sulfur in regeneration for some CuO-containing sorbents

SORBENT PREPARATION

Stepwise incipient wetness technique

Ammonium metavanadate

Calcination for 4 hours under flowing air (40 cc/min)

TABLE I. SORBENT CHARACTERISTICS

Sorbent	Zn:Fe:V Ratio (mass)	Helium Density (g/cm ³)	Surface Area (m ² /g)
ZF-V01-600	25.6:41.9:0.84	5.384	2.854
ZF-V01-750	26.2:42.1:0.77	5.470	1.032
ZF-V03-600	23.9:40.5:2.90	5.357	2.828
ZF-V03-750	24.1:39.4:2.56	5.240	1.006
ZF-V04.8-600	23.1:37.8:3.99	5.149	2.960
ZF-V04.8-750	25.5:40.7:3.96	5.219	0.827
ZF-V15-600			1.934
ZF-V15-750			0.488
Zinc Ferrite	25.8:44.0:0.0	5.140	3.316

RESULTS ON SORBENT PROPERTIES

- Slightly higher Zn/Fe ratios than the original zinc ferrite sorbent.
- Surface areas of the sorbents calcined at 600°C are almost independent of the vanadium percentage and lower than that of the zinc ferrite.
- Sorbents calcined at 750°C have considerably lower surface areas which decrease with the vanadium content.
- Sorbents calcined at the lower temperature;
  - lighter in color,
  - have a lower bulk density,
  - more difficult to dissolve in HCl when preparing samples for atomic absorption tests.

Thus, maybe due to presence of different solid phases.

TEST CONDITIONS

Sulfidation

Temperature: 600°C

Fuel Gas Composition: 1% H₂S

20% H₂

7% H₂O

72% N₂

Regeneration

Temperature: 700°C

Gas Composition: 10% Air

90% N₂

Particle size: -20 - 40 Mesh (425-850 μm)

The test conditions are selected to maximize the positive effect of vanadium on the performance of zinc ferrite sorbent.

RESULTS

Fixed-Bed Reactor Tests

- All sorbents produced prebreakthrough H_2S levels below the detection limit of the fpd for 1 ml gas sample. Hydrogen sulfide levels of 2 ppmv were clearly detectable but 1 ppmv peak was indistinguishable from noise. These results indicate that the obtained desulfurization levels were below the equilibrium levels for zinc oxide.
- Although sorbent ZF-V01-600 showed very good performance in the first cycle, its performance deteriorates rapidly as the cycle number increases.

- Sorbent ZF-V03-600 shows a superior performance in the first four cycles. Its conversion at breakthrough is about the same as that of zinc ferrite for the first cycle, but it has higher conversions than zinc ferrite in second through fourth cycles. Sulfur capture capacity of ZF-V03-600 is slightly below that of zinc ferrite in the first cycle, but its capacity is higher than that of zinc ferrite in the second through fourth cycles and then about the same in the fifth cycle.

- Sorbent ZF-V4.8-600 shows a similar behavior but has somewhat lower conversions until the fourth cycle. In the fifth cycle, it shows superior performance

- Sorbent ZF-V15-600 shows very stable behavior.

- The sulfur capture capacity of the vanadium -promoted zinc ferrite sorbents is considerably higher than the recommended zinc titanate sorbents.

- To check the amount of residual sulfate, second regeneration for ZF-V03-600 and zinc ferrite sorbent was followed by nitrogen purge at the same temperature. For ZF-V03-600 very small amounts of SO_2 was observed, while for zinc ferrite the SO_2 in the nitrogen purge off-gas was about six times larger. The fact that some of the residual sulfate was decomposed, contributed to the improvement in the sulfidation behavior of zinc ferrite in the third cycle.

- Although zinc loss was not quantified for these tests, larger amounts of zinc deposits were present after zinc ferrite sulfidation.

- Nitrogen purge used before oxidative regeneration indicated that vanadium containing sorbents chemisorbed hydrogen sulfide.

- Although not yet quantified, significant amounts of elemental sulfur were collected after the regeneration of vanadium-containing sorbents.

Breakthrough Curves for ZF-V01-600

Inlet H₂S= 1%; P= 1 atm; T= 873K

FIGURE 1.

Breakthrough Curves for ZF-V03-600

Inlet H₂S= 1%; P= 1atm; T= 873K

FIGURE 3. $t^*=393$ min

Breakthrough Curves for ZF-V4.8-600

Inlet H₂S= 1%; P= 1atm; T= 873K

FIGURE 4. $t^*=381$ min

Breakthrough Curves for ZF-V15-600

Inlet H₂S = 1%; P = 1 atm; T = 873K

FIGURE 5. t* = 314 min

Breakthrough Curves for Zinc Ferrite

Inlet H₂S= 1%; P= 1 atm; T= 873K

FIGURE 7. t*=427 min

Breakthrough Curves for Cycle 1

Inlet H₂S = 1%; P = 1 atm; T = 873K

FIGURE 8.

Breakthrough Curves for Cycle 2

Inlet H₂S = 1%; P = 1 atm; T = 873K

FIGURE 9.

Breakthrough Curves for Cycle 3

Inlet H₂S= 1%; P= 1atm; T= 873K

FIGURE 10.

Breakthrough Curves for Cycle 4

Inlet H₂S= 1%; P= 1 atm; T=873K

FIGURE 11.

Breakthrough Curves for Cycle 5

Inlet H₂S= 1%; P= 1 atm; T=873K

FIGURE 12.

TABLE II. CONVERSION AND SORBENT CAPACITY AT A
BREAKTHROUGH OF 10 ppm H₂S FOR CYCLE 1

Sorbent	Conversion, %	Sorbent Capacity, g H ₂ S/g sorbent
ZF-V01-600	87.3	0.319
ZF-V03-600	84.4	0.294
ZF-V4.8-600	74.0	0.244
ZF-V15-600	53.3	0.148
ZF-V4.8-600 (T _s = 923 K)	88.0	0.290
Zinc Ferrite	84.0	0.318
Zinc Titanate	66.2	0.157

TABLE III.   CONVERSION AND SORBENT CAPACITY AT A
BREAKTHROUGH OF 10 ppm H₂S FOR CYCLE 5

Sorbent	Conversion, %	Sorbent Capacity, g H ₂ S/g sorbent
ZF-V01-600	36.3	0.133
ZF-V03-600	57.2	0.200
ZF-V4.8-600	68.9	0.227
ZF-V15-600	53.7	0.149
Zinc Ferrite	57.3	0.217

TABLE IV. CONVERSION AND SORBENT CAPACITY AT A
BREAKTHROUGH OF 50 ppm H₂S FOR CYCLE 1

Sorbent	Conversion, %	Sorbent Capacity, g H ₂ S/g sorbent
ZF-V01-600	88.5	0.324
ZF-V03-600	91.7	0.320
ZF-V4.8-600	77.8	0.256
ZF-V15-600	56.2	0.156
ZF-V4.8-600 (T _s = 923 K)	89.7	0.296
Zinc Ferrite	85.0	0.322
Zinc Titanate	69.3	0.165

TABLE V. CONVERSION AND SORBENT CAPACITY AT A
BREAKTHROUGH OF 50 ppm H₂S FOR CYCLE 5

Sorbent	Conversion, %	Sorbent Capacity, g H ₂ S/g sorbent
ZF-V01-600	38.3	0.140
ZF-V03-600	60.0	0.210
ZF-V4.8-600	72.0	0.237
ZF-V15-600	54.9	0.152
ZF-V4.8-600 (T _s = 923 K)		
Zinc Ferrite	60.7	0.230
Zinc Titanate		

- Effect of Temperature:

1. Increase of temperature from 873 K to 923 K increased the conversion in the first cycle of sulfidation of ZF-V4.8-600, indicating intrinsic kinetic limitation.
2. In the second and third cycles, conversion dropped. This may be due to zinc loss by vaporization or surface area loss due to sintering.
3. Further decrease in conversion at 973 K-sulfidation may be due to the above-mentioned factors. Another factor may be the fact that the reduction of Fe_3O_4 to FeO becomes appreciable around 973 K.

Breakthrough Curves for ZF-V4.8-600

Inlet H₂S= 1%; P= 1 atm

FIGURE 6. $t^*=376$ min

- Surface area of regenerated sorbents higher:
due to surface roughening
- Surface area of sulfided sorbents higher:
due to redispersion of certain phases on other
phases during sulfidation

SURFACE AREAS OF SULFIDED AND REGENERATED SORBENTS

Sorbent	S.A., m ² /g after 2 sulf cycles	S.A., m ² /g after 3 sulf cycles	S.A., m ² /g after 3 sulf-reg cycles	S.A., m ² /g after 5 sulf cycles	S.A., m ² /g after 5 sulf-reg cycles
ZF-V01- 600		1.260			
ZF-V03- 600		1.754			
ZF-V4.8- 600		2.470		1.720	1.490
ZF-V15- 600				2.570	1.240
ZF	2.508		5.81		5.320

CONCLUSIONS

1. Sorbents prepared by the addition of about 4.8 mass % vanadium to zinc ferrite show significantly improved desulfurization performance over zinc ferrite.
2. Sorbents prepared by the addition of about 15 mass % vanadium to zinc ferrite show very stable behavior.
3. Stability increases with an increase in vanadium content.
4. Prebreakthrough H_2S levels below the equilibrium levels for zinc oxide have been attained.
5. Addition of vanadium to zinc ferrite suppresses residual sulfate formation and possibly zinc reduction.
6. Sorbents containing vanadium produce significant quantities of elemental sulfur.
7. Some H_2S is chemisorbed by vanadium oxide.

FUTURE WORK

1. Sorbent Characterization:

- i) XRD analysis of fresh, sulfided and regenerated sorbents to identify the existing solid phases.
- ii) Determination of porosity and pore size distribution of fresh, sulfided and regenerated sorbents.
- iii) Determination of the metallic composition of regenerated sorbents.

2. Fixed-Bed Experiments:

Sulfidation:

Study the effect of:

- i) sulfidation temperature and
- ii) partial pressure of steam.

END

**DATE
FILMED**

11 / 9 / 92