DOE/PC/91309--T6

RECEIVED
FEB 16 1993
C.S.

HIGH TEMPERATURE ALKALI CORROSION OF CERAMICS

IN COAL GAS

DE-FG22-91PC91309

DOE/PC/91309--T6

DE93 007619

Quarterly Progress Report #5
for the Period
September 1, 1992 - December 1, 1992

Prepared by

G.R. Pickrell, T. Sun, and J.J. Brown

Center for Advanced Ceramic Materials
Virginia Polytechnic Institute
and State University
Blacksburg, VA 24061

Prepared for

Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, Pennsylvania 15236

November 24, 1992

"U.S. DOE Patent Clearance is not required prior to
the publication of this document."

MASTER

REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

JP

Objective/Scope

High temperature alkali corrosion has been known to cause premature failure of ceramic components used in advanced high temperature coal combustion systems such as coal gasification and clean-up, coal fired gas turbines, and high efficiency heat engines. The objective of this research is to systematically evaluate the alkali corrosion resistance of the most commonly used structural ceramics including silicon carbide, silicon nitride, cordierite, mullite, alumina, aluminum titanate, zirconia, and fireclay glass. The study consists of identification of the alkali reaction products (phase equilibria) and the kinetics of the alkali reactions as a function of temperature and time.

Technical Progress

I. Phase Equilibria

Stabilized cubic zirconia is often used for high temperature processing because of its good corrosion resistance. The soda-calcia stabilized cubic zirconia (20 mol% calcia) phase relations were investigated in the region from 0-30 wt% soda and from 840-1100°C. The cubic zirconia solid solution was prepared by mixing the appropriate amounts of calcium carbonate and zirconia under acetone. The mixture was dried and fired at successively higher temperatures up to 1500°C, followed by x-ray diffraction analysis of the powders after each firing. After the 1500°C firing, the

calcium stabilized cubic zirconia (CSZ) was the only phase present in the diffraction pattern. Samples used for the alkali reaction study were prepared by repeatedly grinding and mixing appropriate amounts of sodium carbonate and CSZ in acetone with a glass mortar and pestle, drying, and packing into platinum tubes. The samples fired at temperatures higher than 900°C were first calcined at 840°C to remove carbon dioxide from the carbonate, and sealed in platinum tubes, followed by isothermal soaking at temperatures ranging from 900 to 1100°C. The phases formed after the heat treatments and the phase transition temperatures of the soda-CSZ system were determined using x-ray diffraction (XRD) and differential thermal analysis (DTA), respectively.

Table 1 lists the compositions and the phase assemblages of the soda-CSZ reactions at different temperatures. Based on XRD analysis, the reaction products at all temperatures consist of sodium zirconate (Na_2ZrO_3), calcium zirconate (CaZrO_3), and CSZ for compositions containing less than 30% soda. At higher soda content (30%), the phases present are sodium zirconate, calcium zirconate, and unreacted sodium species. It appears that the alkali reaction proceeded by preferentially attacking the zirconia in the calcium-zirconia solid solution (CSZ) with the precipitation of calcium zirconate. The presence of calcium zirconate in all specimens suggests that calcium zirconate has good alkali corrosion resistance at temperatures below 1100°C. To further evaluate the alkali resistance of calcium zirconate, pure calcium zirconate synthesized at 1500°C was mixed with sodium carbonate (20 wt% soda) and fired at 1100°C for 144 h. Only calcium zirconate was detected in the x-ray pattern after the heat treatment.

DTA analysis of the reaction products showed no phase transition between 800-1100°C for all the compositions studied.

II. Alkali Corrosion Kinetics

A new system was developed to conduct the alkali corrosion test because of the inability of the previous bubbler system to completely contain the alkali vapors and severe corrosion problems of the metals used in the bubbler system. The major change in this system compared to the previous systems is the absence of the bubbler, as shown in Figure 1. A longer mullite tube was used to allow a portion of the inlet side to be heated separately with a heating tape to 715°C. An alumina boat filled with sodium nitrate was inserted into the inlet side of the mullite tube (heated to 715°C). The alkali vapors generated from the molten salt were carried to the reaction zone by compressed air, which was pre-filtered to remove carbon dioxide and moisture. The boats were weighed before and after each run to determine the amount of weight loss of the sodium nitrate during the corrosion time interval.

Figure 2. shows the weight loss of the salt as a function of time at 715°C. The weight loss data follow a linear trend ($R^2=0.94$), indicating a constant alkali concentration throughout the reaction. The slope gives a linear weight loss rate of 0.26 g sodium nitrate per hour. Using data from the weight loss and the flow rate of the compressed air, the alkali vapor concentration was calculated to be approximately 0.63 vol%.

The outlet tube was connected to a glass moisture collection chamber immersed

in an ice bath to examine whether or not steam was present in the atmosphere. The flow rate was maintained at 200 cc/min through the glass chamber for 16 hrs during one of the corrosion tests. There was no condensed water present in the collection chamber after the run.

The thickness change of the SiC pellets exposed to the alkali containing atmosphere was measured as described in the previous reports. The reaction thickness of SiC at 1000°C is plotted as a function of time, as shown in Figure 3. The parabolic nature of the data suggests that the reaction is likely to be limited by the diffusion of oxygen through the sodium silicate scale. The oxidation rate of SiC in this case was calculated to be $19.9 \mu\text{m}^2/\text{h}$ according to Figure 4. Compared to the oxidation rate of SiC in air (approximately $0.005 \mu\text{m}^2/\text{h}$ at 1200°C), the oxidation rate of SiC in the presence of alkali was increased by 3 orders of magnitude.

Figure 5 shows the SEM micrographs of the fracture surface of the as received specimen and the surface of the SiC after a 17 h exposure at 1000°C in the alkali containing atmosphere. The SiC is preferentially attacked at the grain boundaries as seen in these micrographs. Figure 6 shows cracking at the interface between the glassy silicate layer and the SiC pellet after reaction at 1000°C. Severe strength reduction can be expected when depletion of the grain boundary phase and interface cracking occur.

Table 1. Phase Analysis of the Soda-CSZ System

<u>Composition (wt%)</u>		Temperature (°C)/ Time (h)	Phases
Zirconia	Soda		
95	5	840 / 100	CSZ + CaZrO ₃ (tr) + Na ₂ ZrO ₃ (tr)
		900 / 96	CSZ + CaZrO ₃ (tr) + Na ₂ ZrO ₃ (tr)
		1000 / 48	CSZ + CaZrO ₃ (tr) + Na ₂ ZrO ₃ (tr)
		1100 / 72	CSZ + CaZrO ₃ (tr) + Na ₂ ZrO ₃ (tr)
90	10	840 / 100	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		900 / 96	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1000 / 48	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1100 / 72	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
85	15	840 / 100	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		900 / 96	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1000 / 48	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1100 / 72	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
80	20	840 / 100	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		900 / 96	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1000 / 48	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
		1100 / 72	CSZ + CaZrO ₃ + Na ₂ ZrO ₃
70	30	840 / 100	CaZrO ₃ + Na ₂ ZrO ₃ + USS
		1000 / 48	CaZrO ₃ + Na ₂ ZrO ₃ + USS

tr = trace, CSZ = Calcia Stabilized Zirconia (cubic), USS = Unreacted Sodium Species

Figure 1. Alkali Vapor Reaction System

Figure 2. Weight loss of sodium nitrate salt as a function of time at 1000°C.

Figure 3. Thickness change versus time for SiC at 1000°C
0.63 vol% alkali concentration.

Figure 4. Thickness squared versus time for SiC at 1000°C
0.63 vol% alkali concentration.

a.)

b.)

Figure 5. SEM micrographs of a.) fracture surface of as received SiC surface b.) 1000°C exposure in 0.63 vol% alkali atmosphere after removal of the glassy layer.

Figure 6. SEM micrograph of the glassy reaction layer formed on the SiC surface after exposure at 1000°C in 0.63 vol% alkali atmosphere.

END

**DATE
FILMED**

3 / 15 / 93