WSRC-TR-92-557

DEUTERIUM ABSORPTION AND MATERIAL PHASE CHARACTERISTICS $Zr_2 Fe (U)$

by A. Nobile

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

WSRC-TR--92-557

DE93 011777

Other Authors:

W. C. Mosley
(WSRC)
J. S. Holder
(WSRC)
K. N. Brooks
(WSRC)

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

**DEUTERIUM ABSORPTION AND MATERIAL PHASE
CHARACTERISTICS OF Zr_2Fe (U)**

A. Nobile, W. C. Mosley, J. S. Holder, and K. N. Brooks

**Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808**

This report was prepared by Westinghouse Savannah River Company (WSRC) for the United States Department of Energy under Contract No. DE-AC09-89SR18035 and is an account of work performed under that contract. Neither the United States Department of Energy, nor WSRC, nor any of their employees makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness, of any information, apparatus, or product or process disclosed herein or represents that its use will not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trademark, name, manufacturer or otherwise does not necessarily constitute or imply endorsement, recommendation, or favoring of name by WSRC or by the United States Government or any agency thereof. The views and opinions of the authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**DEUTERIUM ABSORPTION AND MATERIAL PHASE
CHARACTERISTICS OF Zr_2Fe (U)**

A. Nobile, W. C. Mosley, J. S. Holder, and K. N. Brooks

30 December 1992

1/8/93

Derivative Classifier

Technical Reviewer

Abstract

Deuterium absorption and material phase characteristics of Zr₂Fe (SAES St 198) were studied. Scanning electron microscope images of polished surfaces, electron probe microanalysis, and X-ray powder diffractometry indicated the presence of a continuous Zr₂Fe phase with secondary phases of ZrFe₂, Zr₅FeSn, α-Zr, and Zr₆Fe₃O. A statistically-designed experiment to determine the effects of temperature, time, and vacuum quality on activation of St 198 revealed that when activated at low temperature (350 °C) deuterium absorption rate was slower when the vacuum quality was poor (2.5 Pa vs. 3x10⁻⁴ Pa). However, at higher activation temperature (500 °C), deuterium absorption rate was fast and was independent of vacuum quality. Deuterium pressure-composition-temperature (P-C-T) data are reported for St 198 in the temperature range 200-500 °C. The P-C-T data over the full range of deuterium loading and at temperatures of 350 °C and below is described by the following expression in terms of the equilibrium deuterium absorption pressure, P_{D_2} , and the getter loading, q :

$$K_o e^{-(\Delta H_d/RT)} = \frac{(q^* - q)^2}{P_{D_2} q^2},$$

where ΔH_d and K_o have values of 101.8 kJ·mole⁻¹ and 3.24x10⁻⁸ Pa⁻¹, respectively, and q^* is 15.998 kPa·L⁻¹·g⁻¹. At higher temperatures, one or more secondary reactions in the solid phase occur that slowly consume D₂ from the gas phase. X-ray diffraction and other data suggest these reactions to be:

where 0 < x < 3. Reaction between gas phase deuterium and Zr₂Fe formed in the first reaction accounts for the observed consumption of deuterium from the gas phase by this reaction.

1.0 Introduction

A metal getter having the nominal composition Zr_2Fe , which is produced and sold by SAES Getters under the trade name St 198, has the unique property of being reactive with hydrogen isotopes, oxygen, water, and other gases, while remaining relatively unreactive toward nitrogen. Further, the material is available in the form of pressed pellets that can be used in packed bed reactors with minimal gas pressure drop. These properties allow this getter to be considered a candidate for tritium removal from nitrogen glovebox atmospheres and inert gas process streams with low tritium concentrations. Removal of tritium from glovebox atmospheres with metal getters has the advantage of not forming highly radiotoxic tritiated water, as is the case with conventional glovebox tritium removal systems that catalytically oxidize tritium to water and trap tritiated water on molecular sieves.

Kherani *et al.* (1) studied tritium removal from flowing nitrogen using a SAES St 198/700 purifier cartridge. Tritium in nitrogen with initial concentrations less than $1 \text{ mCi}\cdot\text{m}^{-3}$ was removed to levels undetectable by their ion chamber. However, for initial concentrations higher than $1 \text{ mCi}\cdot\text{m}^{-3}$ tritium breakthrough was observed, and it was further shown that the amount of breakthrough increased with flow rate and initial tritium concentration. A glovebox tritium cleanup system based on the use of St 198 has been designed and built by the Ontario Hydro Research Division (2), and in fact, in a collaborative effort between SAES Getters and Ontario Hydro Research, a tritium cleanup system using St 198 has been designed for commercial sale. Tritium tests on the Ontario Hydro Research glovebox unit demonstrated successful removal of tritium from the glovebox atmosphere. However, tritium breakthrough behavior at higher tritium concentrations, similar to that observed by Kherani *et al.*, was seen.

The above work has demonstrated the usefulness of St 198 for tritium cleanup systems. It is likely that improvements to the getter bed design will eliminate tritium breakthrough at higher concentrations and flow rates. At the Savannah River Site, a program is underway to develop technology that uses metal getters for removing tritium from glovebox and process atmospheres. Our experience in developing metal hydride tritium handling processes has demonstrated that a thorough understanding of hydrogen isotope absorption properties and material phase characteristics of metal hydride forming materials is essential for a number of reasons. This document reports results from a study to characterize the deuterium pressure-composition-temperature (P-C-T) behavior, as well as the material phase characteristics of St 198. Other aspects such as activation of the getter and undesirable secondary reactions that occur in the Zr_2Fe lattice at high temperature while loaded with deuterium were also investigated.

Additionally, we report a number of physical parameters, such as densities and pore structure data that are useful for metal getter reactor design calculations.

Some data on the hydrogen absorption behavior of Zr_2Fe exists in the literature. Manini *et al.* (3) and Boffito *et al.* (4) provide hydrogen absorption isotherms for St 198 at temperatures between 200 and 700 °C. Both of these publications provide correlations that relate the hydrogen absorption pressure to temperature and getter hydrogen content. While the material has a total hydrogen capacity approaching $16 \text{ kPa}\cdot\text{L}\cdot\text{g}^{-1}$, the correlation of Manini *et al.* applies to hydrogen loadings less than $1.5 \text{ kPa}\cdot\text{L}\cdot\text{g}^{-1}$, and the correlation reported by of Boffito *et al.* applies to hydrogen loadings less than $0.66 \text{ kPa}\cdot\text{L}\cdot\text{g}^{-1}$. Manini *et al.* (3) also report that at temperatures higher than 500 °C, hydrogen never reached equilibrium with the material, apparently due to a slow reaction of Zr_2FeH_x to ZrH_2 and ZrFe_2 . These workers further show that at low hydrogen loading only partial conversion of Zr_2FeH_x to ZrH_2 and ZrFe_2 occurs, but at high loadings complete conversion to ZrH_2 and ZrFe_2 occurs. Their samples were held at 500 °C for 2 h. Van Essen and Buchow (5), who investigated hydrogen absorption in several Zr- and Hf-based intermetallic compounds, state that hydrogen uptake in Zr_2Fe does not form a stable hydride, but decomposes to ZrFe_2 and ZrH_2 when activated for 4 h at 50 °C and under 4.05 MPa of hydrogen pressure. Decomposition of hydrogen-loaded Zr_2Fe to ZrFe_2 and ZrH_2 was later confirmed by Aubertin and coworkers (6), who exposed Zr_2Fe at 850 °C to 100 kPa of hydrogen for 15 h.

2. Experimental

Elemental Analysis

St 198 getter in the form of 4 mm long x 6 mm diam. pressed pellets was purchased from SAES Getters, Colorado Springs, Colorado. Solutions obtained by acid dissolution of the getter were analyzed by inductively coupled plasma-mass spectroscopy (ICP-MS) to determine the getter elemental composition. Dissolution of the getter was accomplished by addition of 0.1 g of sample to 8 mL of aqua regia, followed by overnight heating at 95 °C. A remaining residue was then dissolved by adding 2 mL of HF. This solution was then diluted for analysis by ICP-MS. Getter material was also analyzed by X-ray fluorescence (XRF) without standards, but this method is qualitative, and is not expected to be as accurate as ICP-MS.

Pellet Physical Properties

The pore structure of St 198 pellets was characterized with a Micromeritics Auto-Pore II Model 9220 mercury intrusion porosimeter. A number of parameters such as void fractions and densities of pellets, and a packed bed of the as-received pellets were measured.

Material Phase Characteristics

Scanning electron microscopy (SEM) was used to obtain images of polished surfaces on St 198 pellets in order to visually examine the phases present in the material. Energy dispersive X-ray (EDX) analysis yielded qualitative elemental analyses of selected areas on the particle surface. Quantitative analyses of selected areas were obtained by electron probe microanalysis (EPMA). X-ray intensities were compared with zirconium, iron and tin standards using corrections for atomic number, absorption, and fluorescence (ZAF corrections). X-ray diffraction (XRD) was performed on powder obtained from crushing St 198 pellets. Copper K-alpha radiation was used to scan the two theta range from 5 to 135°. Phases were identified by matching crystallographic diffraction peak interplanar spacings (*d*-values) and relative intensities with reference XRD data (7).

Activation Study

The St 198 getter was activated by holding samples under vacuum at temperatures above about 350 °C for several hours. During activation, oxygen in the form of surface oxides diffuses into the bulk, producing a highly reactive clean surface. To determine the optimum activation conditions, the effects of temperature, time, and vacuum quality on activation of the material were investigated by performing a 2³ factorial experiment. Samples were activated at temperatures of 350 and 500 °C, for periods of 4 and 16 h, and under evacuation by a Welch Duo-Seal two stage rotary vane pump (2.5 Pa) or an Alcatel Drytel 30 fluidless vacuum pump (3x10⁻⁴ Pa). A cold trap was not used with either pump. The extent of activation was determined by measuring the initial deuterium absorption rate at 350 °C. High initial deuterium absorption rate is indicative of a well-activated sample. Absorption rate measurements were performed on the gas manifold shown schematically in Figure 1a. Samples (ca. 1 g) were held in the sample cell shown in Figure 1b, which was wrapped with electrical heating tape. A temperature controller kept the sample temperature constant within 1 °C. After activation of the sample, a data acquisition computer recorded pressure vs. time data after opening a valve between the sample and a 300 mL calibrated volume that contained 4000 Pa (30 torr) of deuterium. Pressure was measured with an MKS Baratron 390H 0-133 kPa capacitance manometer.

P-C-T Measurements

Deuterium P-C-T behavior for St 198 samples was investigated using the same gas manifold, sample cell, and sample size described above. Absorption isotherms were measured at temperatures in the range 200 to 500 °C. Prior to each isotherm measurement, a fresh sample was loaded into the sample cell and activated by evacuating with an Alcatel Drytel 30 vacuum pump to $< 3 \times 10^{-4}$ Pa at 350 °C for 4 h. Static absorption isotherm measurements were automated with a data acquisition computer. After admitting an aliquot of gas to the sample, the sample was allowed to equilibrate for 20 minutes. A 0-1.33 kPa MKS Baratron 390H capacitance manometer was used to measure the pressure in equilibrium with the samples.

3. Results

Elemental Analysis

Results from ICP-MS and XRF elemental analyses of St 198 are shown in Table 1. Boffito *et al.* (4) reported St 198 to have the composition 76.5 wt. % Zr, 23.5 wt. % Fe. Our iron analysis agrees closely with that of Boffito *et al.*, but we detect slightly less zirconium, and the presence of some tin (1.2 %). Zn, Cu, Ti, La, and Cr are most likely impurities, and probably don't influence the getter behavior significantly. As will be shown below, tin plays a significant role in the phase behavior of the material. XRF analysis is only qualitative, and does not agree with ICP-MS. However, XRF shows the presence of copper, which was not detected by ICP-MS.

Pellet Physical Properties

St 198 pellets are formed by compacting irregular alloy granules with maximum dimensions of about 150 μm , as shown in Figure 2. Pore size distribution data for St 198 pellets expressed as incremental intrusion volume vs. diameter are shown in Figure 3. The majority of the pores are in the 2 to 5 μm diameter range, with most of the remaining pores being in the 0.2 to 2 μm range. The material has very few pores with diameters less than 0.1 μm . Each 6 mm diam. x 4 mm long St 198 pellet weighed 0.6 g, corresponding to a pellet density of 5.3 $\text{g}\cdot\text{cm}^{-3}$, which is in close agreement with the value of 5.17 measured by porosimetry. The theoretical density of 6.8697 $\text{g}\cdot\text{cm}^{-3}$ measured by porosimetry agrees well with the value of 6.938 $\text{g}\cdot\text{cm}^{-3}$ obtained from X-ray powder diffraction files (7).

The void fraction of 0.25 calculated from the pellet and theoretical densities in Table 2 is slightly lower than the value of 0.31 that we determined from gas expansion measurements. The higher value obtained by gas expansion suggests the presence of small pores not accessible by the mercury intrusion method. However, the close agreement between theoretical densities obtained from the powder diffraction files and porosimetry is inconsistent with inaccessible porosity in the sample, so it is more likely that the deviation is attributable to the larger error associated with the gas expansion technique. Thus, the value from the porosimetry measurements is probably more reliable.

The tap density of a packed bed of 4 mm long x 6 mm diam. pellets was measured to be 2.93 g·mL⁻¹. From this, a void fraction of 0.43 for the bed is calculated, and represents the void fraction associated with volume between individual pellets in the bed.

Material Phase Characteristics

Figure 4 shows an SEM backscattered electron (BSE) image of the polished surface of an St 198 pressed pellet. Phases darker in intensity are of lower atomic number. The primary (continuous) phase of medium density has been determined by EPMA to have the composition $\text{Zr}_{0.660 \pm 0.018}\text{Fe}_{0.337 \pm 0.019}\text{Sn}_{0.003 \pm 0.001}$, that corresponds to Zr_2Fe . The dark secondary phase had the composition $\text{Zr}_{0.350 \pm 0.010}\text{Fe}_{0.650 \pm 0.010}$ that corresponds to ZrFe_2 . Inclusions of a bright secondary phase, consisting mostly of micrometer-wide stringers within the primary phase in regions of eutectic, contained tin in addition to iron and zirconium. EPMA was not able to resolve the small bright inclusions in eutectic regions. Analysis of eutectic areas yielded compositions of 73.3 ± 1.6 atomic percent (a/o) zirconium, 25.5 ± 1.6 a/o iron, and 1.2 ± 0.6 a/o tin. However, three points in the bright secondary phase yielded $\text{Zr}_{0.715 \pm 0.01}\text{Fe}_{0.151 \pm 0.019}\text{Sn}_{0.134 \pm 0.026}$, which corresponds to Zr_5FeSn . Two zirconium-rich points of compositions 79 a/o Zr, 17.7 a/o Fe, 3.3 a/o Sn, and 82.8 a/o Zr, 13.0 a/o Fe, 4.3 a/o Sn were also detected.

An XRD pattern for as-received St 198 is shown in Figure 5, and indicates the presence of the four phases Zr_2Fe , ZrFe_2 , $\alpha\text{-Zr}$, and $\text{Zr}_6\text{Fe}_3\text{O}$ (7). Although $\text{Zr}_6\text{Fe}_3\text{O}$ was not directly detected by EPMA, scattered dark areas within the Zr_2Fe primary phase having average $Z=35.3$ could be attributed to $\text{Zr}_6\text{Fe}_3\text{O}$ (average $Z=31.8$).

Activation Study

Initial absorption rates for activated samples were determined from deuterium pressure vs. time data that was modeled with the rate equation:

$$\frac{RT}{w} \frac{dn_{D_2}}{dt} = \frac{V}{w} \frac{dP}{dt} = k_a P, \quad [1]$$

which when integrated gives the expression:

$$2.303 \log\left(\frac{P}{P_0}\right) = \frac{V}{w} k_a t, \quad [2]$$

where w is the weight of the sample, n_{D_2} is the number of moles of deuterium, V is the system volume, P and P_0 are the pressure and starting pressure, respectively, and k_a is an absorption rate constant. Thus, a plot of $\log(P/P_0)$ vs. time has slope $(V/2.303w)k_a$, and zero intercept. Figure 6 shows pressure vs. time curves for three different sets of activation conditions, and Figure 7 shows $\log(P/P_0)$ vs. time for these data for the first 2 seconds. Once k_a is determined by linear regression of the first 2 seconds of the absorption data, the initial rate ($\text{kPa}\cdot\text{L}\cdot\text{s}^{-1}\cdot\text{g}^{-1}$) is calculated from:

$$\frac{RT}{w} \left(\frac{dn_{D_2}}{dt} \right)_{t=0} = k_a P_0. \quad [3]$$

The various activation conditions studied and the resulting initial deuterium absorption rates from the 2^3 factorial experiment are shown in Table 3. With the exception of samples activated at low temperature and under higher vacuum pressure (oil-sealed rotary vane pump), all initial absorption rates had values between 0.414 and 0.773 $\text{kPa}\cdot\text{L}\cdot\text{s}^{-1}\cdot\text{g}^{-1}$. Samples activated under higher pressure and at low temperature yielded significantly lower initial absorption rates.

The main effects calculated from the statistical test are shown in Table 4. The main effect is a relative number which indicates the relative effect of each variable on the response parameter (initial absorption rate). The larger the main effect, the greater the effect of the variable on the response parameter. Temperature and vacuum conditions have the largest effect on the initial absorption rate, whereas time does not appear affect the activation process significantly.

P-C-T Measurements

Deuterium absorption isotherms for Zr_2Fe at temperatures between 200 and 500 °C are shown in Figure 8. At approximately 6 $\text{kPa}\cdot\text{L}\cdot\text{g}^{-1}$ the slope of the 400 °C isotherm decreases and the isotherm eventually contacts the 350 °C isotherm at approximately 10 $\text{kPa}\cdot\text{L}\cdot\text{g}^{-1}$. Similarly, the isotherm at 500 °C undergoes a slope change at about 5 $\text{kPa}\cdot\text{L}\cdot\text{g}^{-1}$ and nearly contacts the isotherms at 350 and 400 °C. During measurement of the 500 °C isotherm, it was observed that there was initially a rapid equilibration of D_2 with the getter that was complete within a few seconds. However, this was followed by a slow decrease in system pressure. At the lower

temperature (<350 °C) equilibration within a few seconds also occurred, but the final pressure was stable. This observation indicated that initial deuterium equilibration with the sample was rapid, but that a slow solid state reaction was occurring that consumed gas phase deuterium. After running the isotherm again (Figure 9) with a longer equilibration time (1 h) it was apparent that at loadings higher than approximately 2 kPa·L·g⁻¹ a reaction that consumed additional deuterium from the gas phase was occurring. Absorption isotherms at 350 °C run at times of 20 min and 1 h were the same, indicating that the rate of the secondary reaction on the time scale of the isotherm measurement is insignificant at 350 °C.

Further observation of the absorption isotherms in Figure 8 indicates that there appears to be no α -phase-hydride phase transition. The fact that the isotherms are continuous indicates that deuterium absorption occurs by solution of deuterium atoms into the bulk lattice with no abrupt lattice phase transition. Given this, it is possible to describe the equilibrium thermodynamics with a simple chemical equilibrium expression. The following can be written for reaction of deuterium gas with lattice deuterium sites:

where S is a vacant absorption site. The equilibrium expression for this reaction is:

$$K_{eq} = \frac{[DS]^2}{P_{D_2} [S]^2}, \quad [5]$$

where K_{eq} is the equilibrium constant, P_{D_2} is the deuterium partial pressure, and $[S]$ and $[DS]$ are the concentrations of vacant, and deuterium-occupied sites in the metal lattice, respectively. This can also be written in terms of the getter loading, q , and the value of q at full loading, q^* :

$$P_{D_2} = \frac{(q^* - q)^2}{K_{eq} q^2}. \quad [6]$$

A value of 15.998 kPa·L·g⁻¹ was used for q^* . A plot of P_{D_2} vs. $(q^* - q)^2/q^2$ would be a straight line with slope $1/K_{eq}$. Figure 10 shows this plot for the P-C-T data of Figure 8 at temperatures of 350 °C and below. At the higher temperatures, due to the slow reaction occurring in the lattice, the data deviated significantly from the model, so these data were excluded from Figure 10. A van't Hoff plot of the equilibrium constants determined from the slope of the lines in Figure 10 is shown in Figure 11. The value of the equilibrium constant at 400 °C is plotted on Figure 11, and it is seen that this point deviates significantly from the data at lower temperatures. From the slope of this plot, an absorption enthalpy, ΔH_a of 101.8 kJ·mole⁻¹ is calcu-

lated. Thus, the deuterium P-C-T data for the full range of loadings and at temperatures of 350 °C and below are described by:

$$K_0 e^{-(\Delta H_d/RT)} = \frac{(q^* - q)^2}{P_{D_2} q^2}, \quad [7]$$

where K_0 was determined from the intercept of Figure 11 to be $3.24 \times 10^{-8} \text{ Pa}^{-1}$.

X-Ray Diffraction Analysis of Deuterium-Loaded Samples

Samples loaded with deuterium during the absorption isotherm measurements were analyzed by X-ray diffraction to probe changes that occurred from reaction with deuterium. Table 5 shows relative intensities of the strongest X-ray diffraction peaks for several phases in deuterium-loaded samples as a function of temperature. Figure 12 shows diffraction patterns for the samples in Table 5. While Zr_2Fe , ZrFe_2 , $\alpha\text{-Zr}$, and $\text{Zr}_6\text{Fe}_3\text{O}$ are the dominant phases in the as-received material (detected by XRD), the addition of deuterium at 200 °C causes the Zr_2Fe , $\alpha\text{-Zr}$, and $\text{Zr}_6\text{Fe}_3\text{O}$ peaks to disappear. Disappearance of the Zr_2Fe peak is explained by formation of Zr_2FeD_x , as indicated by the Zr_2FeD_x peaks at 200 °C. Alpha-zirconium probably forms ZrD_2 , but the absence of ZrD_2 peaks is surprising, and may be due to formation of amorphous ZrD_2 , or very small ZrD_2 domains. $\text{Zr}_6\text{Fe}_3\text{O}$ which was detected in the as-received material was no longer present in samples exposed to temperatures of 350 °C or less. Disappearance of this phase may come about upon activation, during which oxygen in high concentration regions (surface or oxide phase regions) diffuses into the bulk lattice.

ZrD_2 peaks are absent in the as-received and 200 °C samples, but become apparent in samples exposed at 300 and 350 °C, and become the most intense peaks in the diffraction patterns at 400 and 500 °C. The Zr_2FeD_x peak becomes less intense at 400 °C, and is absent at 500 °C. Thus, on the time scale of our experiments, Zr_2FeD_x is stable at temperatures of 350 °C and below. Above 350 °C, decomposition of Zr_2FeD_x occurs rapidly. The reason for the reappearance of $\text{Zr}_6\text{Fe}_3\text{O}$ peaks at 400 and 500 °C is unclear. Observation of the diffraction patterns, as well as the data in Table 5 does not give a clear indication of an increase in the intensity of the ZrFe_2 peaks, but it appears that there may be an increase in the ZrFe_2 peak intensity at higher temperatures.

4. Discussion

Elemental analysis of St 198 indicated that iron, zirconium, and tin are the major getter components. All other elements are present at impurity levels, and probably do not significantly in-

fluence the deuterium absorption behavior of St 198. Detection of primary Zr_2Fe by SEM and XRD is consistent with the elemental analysis and the Zr-Fe binary phase diagram (8). The phase diagram indicates that elemental zirconium should be the secondary phase in the eutectic. However, EPMA indicates that this secondary phase is Zr_5FeSn , so tin appears to play a role in the eutectic behavior of Zr_2Fe . Since no Zr_5FeSn XRD peaks were detected, it is possible that this phase is amorphous. The cubic phase identified as $\text{Zr}_6\text{Fe}_3\text{O}$ likely results from oxygen contamination of Zr_2Fe . The iron-zirconium phase diagram indicates that at temperatures less than 775°C , Zr_2Fe is unstable and will undergo a transformation to Zr_3Fe and ZrFe_2 . Evidently the kinetics of this transformation is slow since no Zr_3Fe was detected in any of our samples. The absence of Zr_3Fe in our samples is surprising, since it is often detected in cast and annealed binary zirconium-iron alloys with compositions similar to St 198 (9).

Results from the activation study indicate that at the lower activation temperature (350°C) and under poor vacuum conditions, initial deuterium absorption rates were significantly lower. At higher activation temperature (500°C) deuterium absorption rate is not influenced by vacuum conditions, and is rapid for both poor and good vacuum quality. Most likely, the higher gas phase oxygen, water, and other impurity concentrations under poor vacuum conditions cannot be adsorbed and diffused into the bulk at a sufficiently fast rate to maintain a clean and active getter surface. At the higher temperature, adsorption and diffusion of impurities onto the bulk is rapid, and there is little buildup of these impurities on the surface. The main effect value for the influence of activation time on the activation process (Table 4) indicates that time has a very small effect on activation of St 198.

While measuring absorption isotherms at 400 and 500°C , it became apparent that a slow reaction which consumed deuterium might be occurring in the lattice (Figure 9). The XRD results presented in Table 5 and in Figure 12 indicate that on the time scale over which our samples were exposed, decomposition of Zr_2FeD_x begins to occur rapidly above 350°C . While it is clear that this decomposition proceeds with formation of ZrD_2 , the state of the remaining iron is not certain. Previous investigators have indicated that Zr_2FeH_x proceeds with formation of ZrH_2 and ZrFe_2 . Van Essen and Buschow (5) indicate that for 4 h at 50°C and under hydrogen pressure of 4.05 MPa, reaction of hydrogen with Zr_2Fe forms ZrH_2 and ZrFe_2 . Although these authors indicate that results from X-ray diffraction led to this conclusion, the details of their X-ray diffraction were not provided, so it is uncertain from the paper which of the decomposition products (ZrH_2 or ZrFe_2) was detected. It is surprising that the decomposition products were detected at such a low temperature, however the extremely high hydrogen pressure used may be the cause for this. Aubertin *et al.* (6) also report formation of ZrH_2 and ZrFe_2 based on XRD analysis of samples, but their samples were exposed to temperatures of

850 °C, where migration of atoms is sufficiently fast to allow formation of significant quantities of additional phases, such as ZrH₂ and ZrFe₂. Manini *et al.* (3) examined the phases present in Zr₂Fe samples fully- and partially-loaded with hydrogen. XRD analysis of their partially-loaded samples suggest some formation of ZrFe₂, whereas ZrFe₂ peaks in diffraction patterns of the fully-loaded samples were distinct. Their samples were held at 500 °C for 2 h.

Observation of the XRD results in Table 5 and in Figure 12 indicates that while it is clear that ZrD₂ is forming at the higher temperatures, formation of ZrFe₂ at the higher temperatures (> 350 °C) is not obvious. Our samples were exposed to deuterium for about 8 h, which is significantly longer than the samples examined by Manini *et al.* But, the deuterium loading of our samples was not constant, so a straight forward comparison between our samples and those of Manini *et al.* is not possible. However, the 500 °C absorption isotherms in Figure 9 which were collected for equilibration times of 20 min and 1 h indicate that at low loading (<2 kPa.L.g) there is little difference between the two isotherms, but as loading increases the decomposition reaction is more rapid. So apparently, the decomposition reaction rate increases with loading. Thus, it is likely that fully-loaded Zr₂Fe samples examined by Manini *et al.* (3) and Aubertin *et al.* (6) experienced significantly higher decomposition rates due to their full loading.

Our samples are probably similar to the partially-loaded samples of Manini *et al.* which showed minor formation of ZrFe₂. The reaction of deuterium with Zr₂Fe and subsequent decomposition of Zr₂FeD_x to ZrD₂ and ZrFe₂ can be described as follows:

where $0 < x < 3$. The first step is a rapid equilibration, while the second step is slow at low temperatures, and becomes faster at higher temperature. Zr₂Fe formed in Equation [8] subsequently reacts with deuterium from the gas phase to restore the equilibrium concentration of Zr₂FeD_x:

and this explains the observed slow deuterium consumption from the gas phase. Equation [8] predicts stoichiometric formation of ZrFe₂. However, the data in Table 5 indicates that while formation of ZrD₂ is distinct, there is only a slight indication of ZrFe₂ formation, so Equation

[8] cannot fully explain the behavior. It is also possible that Zr_2FeD_x could decompose to ZrD_2 without forming ZrFe_2 . For example:

which would proceed with formation of Fe as well as ZrD_2 . Our XRD results do not detect metallic iron, although iron produced in this reaction might not crystallize to sufficiently large crystals to be detected by XRD. Similar high temperature disproportionation reactions have been observed with other intermetallic compounds, where the element having high hydrogen affinity reacts to form a stable metal hydride. It is likely that both Equations [8] and [10] are occurring.

The inherent instability of the Zr_2Fe compound, as dictated by the Zr-Fe phase diagram (8), indicates that at temperatures less than 775 °C Zr_2Fe should transform to Zr_3Fe and ZrFe_2 in the absence of hydrogen isotopes. In the presence of hydrogen isotopes, decomposition occurs by Equations [8] and [10]. We detected little decomposition of Zr_2Fe in deuterium-loaded samples at 350 °C after about 8 h. However, in recent experiments with St 198 (to be reported in the future) where the material was held at 350 °C while loaded with deuterium for longer periods of time (> 5 days), we see significant decomposition of Zr_2Fe , as indicated by strong ZrD_2 XRD peaks. Thus, decomposition of Zr_2Fe can be expected in applications involving high temperature and significant hydrogen isotope loading. For applications such as tritium removal from glovebox atmospheres or process gas streams, extended exposure of the material to high temperature (350 °C) will be the case, but very low tritium loadings are expected. The data presented in Figure 9 indicates that decomposition of Zr_2Fe at a loadings less than about 2 $\text{kPa}\cdot\text{L}\cdot\text{g}^{-1}$ is slow even at 500 °C.

Although previous investigators have indicated that tritium recovery and regeneration of St 198 capacity can be achieved by heating the alloy to 700 °C under vacuum or under noble gas purge (2), we believe that an investigation is needed to fully characterize this process. Heating tritium-loaded St 198 to high temperature will likely cause the reaction of some tritium to form ZrT_2 . While some tritium will be recovered, it is likely that a portion of the tritium will be converted irreversibly to ZrT_2 . Furthermore, the regenerated material would show a decreased capacity for gettering tritium, and possibly other material differences from the freshly-activated St 198. A further investigation is probably necessary to establish the optimum regeneration conditions.

It was shown above that the P-C-T data can be correlated with a simple equilibrium expression (Equation [7]). While previous investigators have used a different expression to correlate P-C-T data for Zr_2Fe (3,4), Equation [7] represents an improvement to the previous expressions since it applies to the full range of deuterium loadings. Due to secondary reactions occurring in the lattice at temperatures above 350 °C, it is not possible to provide a reliable correlation at temperatures above 350 °C.

Analysis of the P-C-T data resulted in an absorption enthalpy (ΔH_a) of 101.8 kJ·mole⁻¹ D₂. Other investigators have measured ΔH_a values for other SAES getters. ΔH_a for deuterium absorption in St 101 is reported to be 138.2 kJ·mole⁻¹D₂ (10, 11), and ΔH_a for St 707 is 120.6 kJ·mole⁻¹D₂ (10). St 101 has much lower absorption pressures than St 198, and it thus should have a higher absorption enthalpy. The absorption pressures of St 198 are similar to those of St 707, so a similar absorption enthalpy is expected, but the value for St 198 that we report is lower than that of Boffito *et al.* (10). However, the absorption enthalpy reported by Boffito *et al.* was determined from P-C-T data for low deuterium loading in the alloy. Our absorption enthalpy result for St 198 was extracted from P-C-T data covering the full deuterium capacity of the alloy. Due to repulsive interaction effects between deuterons in the metal lattice, the absorption enthalpy is most likely a function of the alloy deuterium loading. Repulsive interactions would likely cause lower absorption enthalpy at higher deuterium loading, and this may be the reason for our lower absorption enthalpy value.

5. Conclusion

St 198 consists mostly of the Zr_2Fe phase with secondary phases of ZrFe_2 , Zr_5FeSn , $\alpha\text{-Zr}$, and $\text{Zr}_6\text{Fe}_3\text{O}$. The material becomes well activated when evacuated at temperatures higher than 350 °C for 4 h or longer, as long as a relatively high vacuum is maintained. Higher activation temperatures should be considered for systems with poorer vacuum quality. Deuterium P-C-T data for the full range of getter deuterium loadings and at temperatures of 350 °C or lower can be correlated using a simple equilibrium expression. At temperatures higher than 350 °C, Zr_2FeD_x decomposes at a significant rate to ZrD_2 , and possibly ZrFe_2 and Fe. However, for applications involving very low hydrogen isotope loading, such as stripping low tritium concentrations from glovebox or process atmospheres, the decomposition reaction probably would be insignificant. Recovery of tritium absorbed on St 198 by heating under vacuum at temperatures higher than 500 °C would likely cause decomposition of Zr_2FeT_x with the formation of irreversible ZrT_2 , and a decreased capacity of the regenerated material. An investigation is necessary to establish the feasibility and optimum conditions for recovering hydrogen isotopes from St 198.

Acknowledgements

The authors wish to thank many individuals for contributions to this work. Mercury porosimetry was performed by R. A. Malstrom, bulk elemental analyses by ICP-MS and XRF were provided by C. J. Coleman and A. R. Jurgensen, respectively. F. E. Odum and A. S. Holston prepared the samples for SEM and EPMA. SEM examination was performed by A. S. Holston and J. E. Durden. EPMA was performed by L. F. Tovo and S. F. McDaniel. A. R. Jurgensen and R. E. Howell provided the XRD analyses. W. L. Moyer assisted with the activation study and P-C-T measurements.

References

1. Kherani, N. P., Shmayda, W. T., and Jalbert, R. A., *Proceedings of the 12th Symposium on Fusion Engineering*, Monterey, Ca., October 12-16, 1987, I. E. Conf. No. 11702.
2. Shmayda, W. T., Kherani, N. P., Wallace, B., and Mazza, F., *Fusion Technology Vol. 21*, 616 (1992).
3. Manini, P., Boffito, C., Gasparini, G., Maran, C., Gallitognotta, A., *Proceedings of the 2nd European Vacuum Conference*, Trieste, 1990.
4. Boffito, C., Doni, F., and Rosai, L., *Journal of the Less-Common Metals* 104, 149, (1984).
5. Van Essen, R. M., and Buschow, K. H. J., *Journal of the Less-Common Metals* 64, 277, (1979).
6. Aubertin, F., Gonser, U., and Campbell, S. J., *Journal of the Less-Common Metals* 101, 437, (1984).
7. Powder Diffraction Files compiled by the JCPDS - International Center for Diffraction Data.
8. Massalski, T. B., Editor-in-Chief, "Binary Alloy Phase Diagrams", Second Edition, Volume 3, p. 1798, ASM International, 1990.
9. Malakhova, T. O., and Alekseyeva, Z. M., *Journal of the Less-Common Metals* 81 293 (1981).
10. Boffito, C., Ferrario, B., and Martelli, D., *Journal of Vacuum Science and Technology A* 1 (2), 1279 (1983).
11. Knize, R. J., *Journal of Vacuum Science and Technology* 20, 1135 (1982).

Table 1. Elemental analysis of as-received SAES St 198 by inductively coupled plasma mass spectroscopy (ICP-MS) and X-ray fluorescence (XRF).

ELEMENT	WEIGHT PERCENT	
	ICP-MS	XRF
Zr	73.6	81.8
Fe	23.3	16.9
Sn	1.2	1.0
Zn	0.5	-
Cu	-	0.3
Ti	0.1	-
La	0.07	-
Cr	0.06	-

Table 2. Summary of as-received SAES St 198 pellet physical characterization parameters.

PROPERTY	VALUE
Total intrusion volume	0.0479 mL·g ⁻¹
Total pore area	2.523 m ² ·g ⁻¹
Median pore diam. (vol)	2.8443 μm
Median pore diam. (area)	0.0042 μm
Average pore diam. (4V/A)	0.0759 μm
Pellet density	5.1689 g·mL ⁻¹
Theoretical density	6.8697 g·mL ⁻¹
Pellet void fraction	0.25
Packed bed void fraction (4mm x 6mm pellets)	0.43

Table 3. Test matrix and results for 2³ factorial getter activation test.

RUN	TEMPERATURE (°C)	ACTIVATION TIME (h)	VAC PRESS (Pa)	RATE (kPa·L·s ⁻¹ ·g ⁻¹)
1	500	4	2.5	0.7468
2	500	4	3x10 ⁻⁴	0.5377
3	500	16	2.5	0.4140
4	500	16	3x10 ⁻⁴	0.7730
5	350	4	2.5	0.0430
6	350	4	3x10 ⁻⁴	0.6028
7	350	16	2.5	0.0017
8	350	16	3x10 ⁻⁴	0.6829

Table 4. Main effect values determined from 2^3 factorial test.

VARIABLE	MAIN EFFECT
Temperature	0.285
Time	-0.015
Vacuum Condition	-0.348

Table 5. Relative intensities of the strongest X-ray diffraction peaks for as-received and deuterium-exposed SAES St 198.

PHASE:	Zr ₂ Fe	ZrFe ₂	α-Zr	Zr ₆ Fe ₃ O	Zr ₂ FeD _x	ZrD _{1.8}
ABSORPTION TEMPERATURE (°C)						
as-received	100	76	49	53	0	0
200	0	23	0	0	100	0
300	0	24	0	0	100	24
350	0	34	0	0	100	21
400	0	55	0	38	29	100
500	0	57	0	35	0	100

Figure Captions

- Figure 1. (a) Schematic arrangement of the apparatus used for activation and P-C-T studies on St 198 samples, (b) sample cell.
- Figure 2. SEM image of an as-received SAES St 198 pellet surface.
- Figure 3. Incremental intrusion volume vs. pore diameter for as-received SAES St 198 pellets.
- Figure 4. SEM BSE image and elemental maps of the polished surface of an as-received St 198 pellet.
- Figure 5. X-ray powder diffraction patterns of SAES St 198 powder obtained from pulverization of as-received pellets.
- Figure 6. Deuterium pressure vs. time data for three sets of conditions in the 2^3 factorial test.
- Figure 7. $\text{Log}(P/P_0)$ vs. time plots used to determine initial deuterium absorption rate in the 2^3 factorial test.
- Figure 8. Deuterium absorption isotherms for SAES St 198.
- Figure 9. Deuterium absorption isotherms at 500 °C for equilibration times of 20 min and 1 h for SAES St 198.
- Figure 10. Absorption pressure vs. $q^2/(q^*-q)$ for SAES St 198 at temperatures of 200, 300, and 350 °C.
- Figure 11. van't Hoff plot of the equilibrium constants.
- Figure 12. X-ray powder diffraction patterns of SAES St 198 samples after conducting absorption isotherms at 200 and 500 °C.

DISTRIEUTION:

J. R. Knight, 773-A
T. Motyka, 773-A
R. H. Hsu, 232-H
A. F. Reichman, 773-A
M. W. Lee, 773-A
J. H. Owen, 773-A
A. Nobile, LANL, MST-3, C 348
W. C. Mosley, 773-A
J. S. Holder, 232-H
K. N. Brooks, 234-H
J. R. Wermer, 232-H
J. E. Klein, 773-A

Stk Contact Clanton Mosley, 5-2404

Figure 2. ~~SEM~~ ~~SEM~~ image of St 198 pellet surface

Fig. 2

Figure 4. SEM BSE image and elemental maps of St198.

Clanton Mosley 5-2404
124

Figure 5. X-ray powder diffraction patterns of as-received St-196 powder.

24.7.15
 Clanton Mosley 5-2404

Fig. 6

Figure 9. X-ray powder diffraction patterns of St 198 samples after conducting absorption isotherms at 200 and 500 °C.

3029 Fig 12 Clanton Maslog
 5-2404

END

DATE
FILMED

6 / 15 / 93