DOE/PC/90295--T9

FEB 05 1993

PYRITE SURFACE CHARACTERIZATION AND
CONTROL FOR ADVANCED FINE COAL
DESULFURIZATION TECHNOLOGIES

DOE/PC/90295--T9

DE93 011633

DOE Grant No: DE-FG22-90PC90295

Ninth Quarterly Technical Progress Report
(from Sept.1, 1992 to Dec. 31, 1992)

by

X. H. Wang (Principal Investigator)
J. W. Leonard and B.K. Parekh (Co-PIs).
and C.L. Jiang (Graduate Student)

Department of Mining Engineering and
Center for Applied Energy Research,
University of Kentucky,
Lexington, Kentucky 40506

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

FEB 05 1993

PYRITE SURFACE CHARACTERIZATION AND
CONTROL FOR ADVANCED FINE COAL
DESULFURIZATION TECHNOLOGIES

DOE Grant No: DE-FG22-90PC90295

Ninth Quarterly Technical Progress Report
(from Sept.1, 1992 to Dec. 31, 1992)

by

X. H. Wang (Principal Investigator)
J. W. Leonard and B.K. Parekh (Co-PIs).
and C.L. Jiang (Graduate Student)

Department of Mining Engineering and
Center for Applied Energy Research,
University of Kentucky,
Lexington, Kentucky 40506

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY

This is the 9th quarterly technical progress report for the project entitled "Pyrite surface characterization and control for advanced fine coal desulfurization technologies", DE-FG22-90PC90295. The work presented in this report was performed from September 1, 1992 to November 31, 1992.

The objective of the project is to conduct extensive fundamental studies on the surface chemistry of pyrite oxidation and flotation and to understand how the alteration of the coal-pyrite surface affects the efficiency of pyrite rejection in coal flotation. During this reporting period, the surface oxidation of pyrite in various electrolytes was investigated. It has been demonstrated, for the first time, that borate, a pH buffer and electrolyte used by many previous investigators in studying sulfide mineral oxidation, actively participates in the surface oxidation of pyrite. In borate solutions, the surface oxidation of pyrite is strongly enhanced. The anodic oxidation potential of pyrite is lowered by more than 0.4 volts. The initial reaction of the borate enhanced pyrite oxidation can be described by:

This reaction is irreversible and is controlled by the mass-transfer of borate species from the solution to the surface. It has been shown that the above reaction inhibits the adsorption of xanthate on pyrite. Comparative studies have been made with other sulfide minerals. The solution chemistry of the iron-borate systems have been studied to understand the electrochemical results.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

INTRODUCTION

Surface-based physical separation techniques such as froth flotation and agglomeration have shown the potential for removing pyritic sulfur from coal. However, the efficiency of these techniques in rejecting pyrite from fine coal has been very poor. The main cause of the difficulties of pyrite separation from coal has been attributed to the oxidation of pyrite surface. It has been shown that when pyrite surfaces are subjected to mild oxidation, the floatability of pyrite increases. This has been attributed to the formation of a sulfur-rich layer on the pyrite surface. A detailed understanding of the fundamental processes of pyrite surface oxidation is thus very important for fine coal cleaning. During this reporting period, the surface oxidation of pyrite in various electrolytes have been studied. The studies demonstrate that the pH buffers, such as sodium borate, sodium bicarbonate, phosphate, have very profound influence on the oxidation of pyrite and the adsorption of xanthate collectors.

DESCRIPTION OF EXPERIMENTAL TECHNIQUES

Electrochemical techniques have been widely used to study the nature, mechanisms and kinetics of redox reactions at sulfide surfaces. The following electrochemical techniques have been used in the present research: cyclic voltammetry, steady state polarization, chronopotentiometry and AC impedance/capacitance spectroscopy. The principles and usefulness of these techniques have been described in several electrochemistry textbooks [e.g., 1].

A. Electrochemical Set-UP

A standard three-electrode system is used in this research. A pyrite electrode is the working electrode. The counter electrode is a platinum electrode. The potentials were measured against a saturated calomel electrode (SCE) which potential is related to the standard hydrogen scale by the following equation:

$$E_{SCE} \equiv E_h - 245 \text{ (mV)}$$

The electrochemical system used in the present study consists of an EG&G Princeton Applied Research (PAR) Model 273 potentiostat/galvanostat and a PAR model 660 rotating-disc electrode apparatus. The system, including data acquisition, is operated by a 386 IBM computer. All other measurements were performed with a user-modified Headstart Creative Software. The rotating-disc electrode (RDE) technique enable one to study the effect of rotating the electrode on the reaction processes occurring at the electrode surface, and thereby to distinguish the solution species involved reactions from solid species reactions. The EG&G Princeton Applied Research manufactured RDE system has several drawbacks. Therefore, the RDE has been modified so that only the lower portion of the shaft rotates, while the upper part remains stationary. This enables the upper portion to keep tight contact with the cell lip. The cell will thus be sealed from the ambient, which prevent any oxygen/air entrance into the electrochemical cell. The atmosphere in the cell can be well controlled.

B. Pyrite Electrodes

The respective pyrite samples were cut to a cubic shape and were attached to brass rods using conducting carbon glue. The electrodes were molded in epoxy resin and one face was initially ground using SiC polishing papers 600 and 1000 grit to expose to the electrolyte. Before each measurement, the electrode was polished using 4000 grit SiC polishing paper in air with distilled deionized water, and rinsed first with ethanol and then with distilled-deionized water. The measured geometric surface areas were used for calculating the current density.

C. AC Impedance Measurements

AC impedance spectroscopy is one of the few technique available for in-situ characterization of solid/liquid interfaces. This technique is based on measurement of current through an electrode when a sinusoidal potential is applied. If the applied potential is

$$E = \delta E \sin (\omega t)$$

where δE is the amplitude of the AC signal, ω is the angular frequency and t is the time. The current flux is given by:

$$i = \delta i \sin (\omega t + \theta)$$

where δi is the amplitude of current and θ is the phase angle. From this, the impedance can be calculated by

$$Z = dE/di = Z' + j \omega Z''$$

Therefore, AC impedance involves measurement of the impedance (Z , or Z' and Z'') as a function of frequency. From the measured data, the parameters related to the interfacial reactions, like rate constants, double layer capacitance and the reaction mechanisms/products can be determined.

AC impedance technique has been extensively used for studying corrosion problems. Application of AC to the study of sulfide oxidation is relatively new [2]. The experimental system used in this investigation consists of the PAR Model 273 potentiostat and Saltron 1255 Frequency Response Analyzer (FRA). The measurements have been carried out using the EG&G PAR M378/388 software package. The equivalence circuit analysis was performed using the computer code EQUIVCRT, developed by the University of Twente, Netherlands.

Results And Discussion

Sodium borate (NaBO_3 or $\text{Na}_2\text{B}_4\text{O}_7$), a strong pH buffer at $\text{pH}=9.2$, has been used as the electrolyte by many previous investigators in studying the electrochemistry of sulfide minerals. Our literature survey showed that over 95 percent of the publications on metal sulfide electrochemistry in alkaline solutions were performed in the sodium tetraborate solutions. The concentration of sodium borate used in previous studies was in the range from 1×10^{-2} M to 1.0 M. In all the cases, the buffer/electrolyte was regarded as an inactive chemical, and its possible effects on the electrochemical oxidations of pyrite have been completely neglected.

During this reporting period, the effects of various electrolytes and pH buffers on the surface oxidation of pyrite have been studied. Our particular emphasis has been to investigate the oxidation of pyrite in alkaline solutions in the absence and presence of sodium borate as a pH buffer.

Figure 1 shows the cyclic voltammograms of pyrite in KClO_4 electrolyte solution in the absence and presence of varying concentrations of sodium borate as a pH buffer. In the absence of sodium borate, only one anodic current peak is seen at potential above 0.4 Volt (vs SCE), which is attributed to the oxidation of pyrite. Similar results have been obtained in NaNO_3 electrolyte solution, as shown in Fig.2. It can be seen that there is no significant difference in the voltammograms obtained in the NaNO_3 and KClO_4 , respectively. In the presence of borate, an additional anodic peak (labelled as peak II in Fig.1) appears at $E_p = 250$ mV (vs SCE). As can be seen from Fig.1, the peak current of peak II increases with increasing borate concentration. In extremely high concentrations of sodium borate, the two oxidation peaks merge into one, as shown in Fig. 3. On a rotating disc electrode, peak II becomes a plateau, as shown Fig.4. Figure 5 shows that the limiting current is nearly a linear function of the square root of the rotation speed. These characteristic features of the pyrite oxidation in borate-containing solution demonstrate that borate species is involved in the pyrite oxidation process. Furthermore, from the Tafel plots, it may be concluded that the rate-determining step is an irreversible single-electron transfer reaction. We thus propose that in the presence of borate, the initial oxidation of pyrite is due to the following reaction:

In order to further understand these processes, the solution chemistry of the borate-water and borate-iron systems has also been investigated. It was found that the chemistry of borate is much more complex than it is generally believed. Besides the protonation reactions of borate, borate undergoes polymerization under high concentrations to form a number of polymers, $\text{B}_3\text{O}_3(\text{OH})_4^-$; $\text{B}_3\text{O}_3(\text{OH})_5^-$; $\text{B}_4\text{O}_5(\text{OH})_4^{2-}$ and $\text{B}_5\text{O}_6(\text{OH})_4^-$. Figure 6 presents the concentration-pH distribution diagrams for the borate-water system at two

different borate concentrations. It can be seen that at high concentrations, all the polyborates exist in high quantities. More importantly, borate is a strong complexing agent for heavy metal ions such as Fe^{3+} , Pb^{2+} , and Cu^{2+} . As shown in Table I, borate reacts with the heavy metal ions and forms both soluble and insoluble metal-borate compounds. In Figs. 7 and 8, the iron species distributions in the absence and presence of 0.1 M borate are compared, in which the borate concentration match with that used in most previous investigations. It can be seen that in the presence of borate, even ferric hydroxide is unstable. It dissolves to form a number of ferric borate species. The precipitation pH of $\text{Fe}(\text{OH})_3(\text{s})$ shifts from pH=3 to pH=7--9, respectively. It is then evident that due to the formation of such soluble complex, the oxidation of pyrite will be enhanced.

The enhancement of pyrite surface oxidation by borate species is also clearly demonstrated by the AC impedance measurements. Figure 9 presents the Nyquist plots for pyrite at pH=9.4 in the absence and presence of 1×10^{-3} M borate as a pH buffer. Note that the charge transfer resistance (R_{CT}) and the exchanging current density I_0 is related by the following equation [1]:

$$R_{CT} = \frac{RT}{n F I_0}$$

Thus, the charge transfer resistance, R_{CT} is a measure of the rate of the electrode reaction. The smaller the R_{CT} is, the greater the reaction rate of surface oxidation will be. From the results presented in Fig.9, it can be seen that the presence of borate substantially increases the oxidation rate of pyrite.

Comparative electrochemical studies have been carried out with other metal sulfides, such as lead sulfide and copper sulfides to examine the effects of borate on their surface oxidation. Figure 10 compares the voltammograms for galena in the 0.1 M KClO_4 and $\text{Na}_2\text{B}_4\text{O}_7$ electrolyte solution. It can be seen that borate strongly affects the oxidation of galena. In potassium perchlorate solution, the anodic current increases sharply with the applied potential. No passivation can be observed. However, in borate solution, the oxidation of galena retains a "plateau-like" anodic current after the first stage oxidation.

On the rotating-disc electrode, the current limit is increased. The results clearly indicate that the electrode oxidation is largely inhibited by the formation of some passivating oxidation layers. Based on the data given in table I, distribution diagrams similar to that of Fig.7 were also constructed. The results revealed that in these cases, the insoluble products, such as $\text{Pb}(\text{OH})[\text{B}(\text{OH})_4](\text{s})$, are the predominant species. They are more stable than the corresponding metal hydroxides. Thus, the oxidation of lead sulfide in a borate electrolyte solution are found to be strongly inhibited. Similar results were obtained with copper sulfides.

The above results clearly demonstrate, for the first time, that the pH buffers/electrolyte have a strong affinity to pyrite and other sulfide minerals. Their roles in the oxidation of pyrite should not be overlooked if the measurements are carried out in such systems. Unfortunately, our literature reviews indicate that in almost all the previous studies on pyrite oxidation, the measurements were performed using high concentrations (from 0.01M to 1.0 M) of pH buffers, many even used them as the supporting electrolytes. Moreover, in most of the studies, the buffers were treated as "inactive" chemicals and their effects on pyrite surface oxidation were completely neglected. Hence, such studies could have provided misleading interpretations and conclusions, and should be regarded with great caution.

For example, a number of investigators studied the reaction of pyrite with xanthates in order to elucidate the reaction mechanisms and products related to pyrite flotation with xanthates [7-9]. These studies concluded that dixanthogen is physically adsorbed on pyrite surface, and is the only product formed on pyrite surfaces and responsible for pyrite flotation. However, more recent studies by Wang [10], Wang et al [11,12], Ralston et al [13], Fuerstenau et al [14,15] and Trahar [16] indicate that a number of surface iron-xanthate compounds can be formed on pyrite surface and these compounds play important roles in pyrite flotation. A survey of the published literature revealed that all the previous electrochemical studies of xanthate adsorption on pyrite surface were carried out in high concentration borate solution, i.e., using borate as the electrolyte, and the possible effects of borate on xanthate adsorption were not considered. It is thus of great

importance to conduct systematic studies of influence of borate on xanthate-pyrite interactions.

Figure 11 shows the cyclic voltammograms of pyrite in KClO_4 solution in the absence and presence of $1 \times 10^{-3} \text{ M}$ xanthate. It has been shown in our previous studies [17-20] that the initial oxidation of pyrite in KClO_4 electrolyte solution takes place through the chemisorption of hydroxide ions:

In the presence of xanthate, an anodic current peak commences at $E = -0.2 \text{ Volt vs SCE}$. The peak potential is at about 0.1 volt vs SCE . After which, the anodic current increases again, but current density is smaller than that observed in the absence of xanthate. This indicate some passivating effects of the formed products on the surface oxidation of pyrite. On the rotating-disc electrode, the anodic current increases with increasing the rotation speed, However, the limiting current is poorly defined, as shown in Fig.12. Figure 13 compares two voltammograms recorded on platinum and pyrite electrodes, respectively, in the same solution. It can be seen that the anodic current of xanthate oxidation into dixanthogen on the platinum electrode commences at about 0.2 volt more positive than that on pyrite. The reversible potential of xanthate oxidation to dixanthogen at this concentration is about 0 volt vs SCE (0.25 volt vs SHE). More importantly, no reduction of dixanthogen to xanthate has been observed on pyrite. This is contrary to previous studies [8] in which the reduction of dixanthogen was observed. These results suggest that the adsorption of xanthate on pyrite is irreversible, and that products other than dixanthogen might have been formed on the pyrite surfaces. It has been preliminarily proposed that the adsorption of xanthate on pyrite takes place through the following reaction:

The exact reaction and products are being investigated at present.

Figures 14 and 15 show the effects of borate on the interaction between pyrite and xanthate. At low borate concentrations, the effect is not very profound. When the borate concentration is higher than that of xanthate, the adsorption of xanthate is apparently suppressed. At extremely high borate concentration (0.1 M), almost no difference could be observed between the voltammograms obtained in the absence and presence of xanthate. These results clearly indicate that the adsorption of xanthate is completely depressed. Therefore, borate, either used as a pH buffer or as electrolyte, has strong interaction with pyrite and will inhibit the interaction between pyrite and xanthate. This is readily understandable if we compare reactions (I), (II) and (III). It can be seen the adsorption of these anions--borate, hydroxide or xanthate--on pyrite surfaces follows the same principle. These anions will compete with other. Which species and reaction will be dominant will depend on the concentration of that species in the solution. Thus, borate is a depressant for pyrite flotation with xanthate.

Table I Stability Constants of Borate Compounds

Reaction	log K	Ref
I. Borate-Water System		
$H^+ + B(OH)_4^- \rightleftharpoons HB(OH)_4 \text{ (or } B(OH)_3 + H_2O)$	9.236	3
$2H^+ + 3B(OH)_4^- \rightleftharpoons B_3O_3(OH)_4^- + 5H_2O$	20.07 (I=1.0)	3
$H^+ + 3B(OH)_4^- \rightleftharpoons B_3O_3(OH)_5^- + 4H_2O$	10.40 (I=1.0)	3
$2H^+ + 4B(OH)_4^- \rightleftharpoons B_4O_5(OH)_4^{2-} + 7H_2O$	20.90 (I=1.0)	3
$4H^+ + 5B(OH)_4^- \rightleftharpoons B_5O_6(OH)_4^- + 10H_2O$	38.20 (I=1.0)	3
II. Borate-Iron System		
$Fe^{3+} + B(OH)_4^- \rightleftharpoons Fe[B(OH)_4]^{2+}$	8.58 (I=1.0)	4
$Fe^{3+} + 2B(OH)_4^- \rightleftharpoons Fe[B(OH)_4]_2^+$	15.54 (I=1.0)	4
$Fe^{3+} + 3B(OH)_4^- \rightleftharpoons Fe[B(OH)_4]_3$	20.6 (I=1.0)	5
III. Borate-Copper System		
$Cu^{2+} + B(OH)_4^- \rightleftharpoons Cu[B(OH)_4]^+$	7.13 (I=1.0)	5
$Cu^{2+} + 2B(OH)_4^- \rightleftharpoons Cu[B(OH)_4]_2$	12.45 (I=1.0)	5
$Cu^{2+} + 3B(OH)_4^- \rightleftharpoons Cu[B(OH)_4]_3^-$	15.27 (I=1.0)	5
$Cu(OH)[B(OH)_4](s) \rightleftharpoons Cu^{2+} + OH^- + B(OH)_4^-$	-17.3	5
$Cu[B(OH)_4]_2(s) \rightleftharpoons Cu^{2+} + 2B(OH)_4^-$	-14.5	5
IV. Borate-Lead System		
$Pb^{2+} + B(OH)_4^- \rightleftharpoons Pb[B(OH)_4]^+$	5.21	5
$Pb^{2+} + 2B(OH)_4^- \rightleftharpoons Pb[B(OH)_4]_2$	(I=1.0) 6	
$Pb^{2+} + 3B(OH)_4^- \rightleftharpoons Pb[B(OH)_4]_3^-$	11.17 (I=1.0)	4
$Pb(OH)[B(OH)_4](s) \rightleftharpoons Pb^{2+} + OH^- + B(OH)_4^-$	possible ?	
$Pb[B(OH)_4]_2(s) \rightleftharpoons Pb^{2+} + 2B(OH)_4^-$	-10.78	4

IV. Borate-Al system

$\text{Al}^{3+} + \text{B}(\text{OH})_4^- \rightleftharpoons \text{Al}[\text{B}(\text{OH})_4]^{2+}$	7.62 (I=1.0)	4
$\text{Al}^{3+} + 2\text{B}(\text{OH})_4^- \rightleftharpoons \text{Al}[\text{B}(\text{OH})_4]_2^+$	14.64 (I=1.0)	4
$\text{Al}^{3+} + 3\text{B}(\text{OH})_4^- \rightleftharpoons \text{Al}[\text{B}(\text{OH})_4]_3$	20 (I=1.0)	4
$\text{Al}^{3+} + 6\text{B}(\text{OH})_4^- \rightleftharpoons \text{Al}[\text{B}(\text{OH})_4]_6^{3-}$	38.54 (I=1.0)	4
$\text{Al}[\text{B}(\text{OH})_4]_3(\text{s}) \rightleftharpoons \text{Al}^{3+} + 3\text{B}(\text{OH})_4^-$	-22.92	4

V. Borate-Zn system

$\text{Zn}^{2+} + \text{B}(\text{OH})_4^- \rightleftharpoons \text{Zn}[\text{B}(\text{OH})_4]^+$		4
$\text{Zn}^{2+} + 2\text{B}(\text{OH})_4^- \rightleftharpoons \text{Zn}[\text{B}(\text{OH})_4]_2$	(I=1.0) 6	
$\text{Zn}^{2+} + 3\text{B}(\text{OH})_4^- \rightleftharpoons \text{Zn}[\text{B}(\text{OH})_4]_3^-$	8.44 (I=1.0)	4
$\text{Zn}^{2+} + 4\text{B}(\text{OH})_4^- \rightleftharpoons \text{Zn}[\text{B}(\text{OH})_4]_4^{2-}$	11.8 (I=1.0)	4
$\text{Zn}(\text{OH})[\text{B}(\text{OH})_4](\text{s}) \rightleftharpoons \text{Zn}^{2+} + \text{OH}^- + \text{B}(\text{OH})_4^-$	possible ?	
$\text{Zn}[\text{B}(\text{OH})_4]_2(\text{s}) \rightleftharpoons \text{Zn}^{2+} + 2\text{B}(\text{OH})_4^-$	-8.78	4

REFERENCES

1. Bard, A. and Faulkner, L.R., (1980), *Electrochemical Methods: Fundamentals and Applications*. John Wiley & Sons, 705pp.
2. Chander, S. and Aplan, F.F., (1990), *Surface and Electrochemical Studies in Coal Cleaning*, Final Report, DE-FG22-85PC80523. 97pp.
3. Smith, R.M. and Martell, A.E., 1979. *Critical stability constants*. Vol.4, Inorganic ligands. New York. Plenum Press.
4. Sillen, L.G. and Martell, A. E. (1964), *Stability constants of metal-ion complexes*. The Chemical Society, Special publication No.17. London.
5. Sillen, L.G. and Martell, A. E., (1970), *Stability constants of metal-ion complexes*. The Chemical Society. Special publication No.25. London.
6. Hogfeldt, E. (1982), *Stability constants of metal-ion complexes*. Part A: Inorganic ligands. Pergamon press.
7. Fuerstenau, M.C., Kuhn, M.C. and Elgillani D.A., (1968), the role of dixanthogen in xanthate flotation of pyrite. *Trans AIME*. Vol.241:148-156.
8. Woods, R., 1976, *Electrochemistry of Sulfide flotation*. in M.C. Fouerstenau (ed.), *Flotation*. AIME, Vol.I, pp298-333.
9. Ball, B. and Richard, R.S., 1976, *The chemistry of pyrite flotation and depression*. in M.C. Fuerstenau (ed.), *Flotation*. AIME. Vol. I, pp458-484.
10. Wang, X.H., (1989), *The chemistry of Flotation, Activation and Depression of Iron-Containing Sulfide Minerals*. Ph.D. Thesis, Lulea University, Sweden. 514pp.
11. Wang, X.H., Forssberg, E and Bolin, N.J., (1989), *Thermodynamic calculations on iron-containing sulfide minerals flotation systems*. I: The stability of iron xanthates. *Int. J. Miner. Process*. Vol.27, 1-19.
12. Wang, X.H. and Forssberg, E., (1992) *Mechanisms of pyrite flotation with xanthates*. *Int. J. Miner. Process.*, vol.
13. Fornasiero, D. and Ralston J. (1992), *The interaction of ethylxanthate with pyrite*. In P.E. Richardson and R. Woods (eds.), *Electrochemistry in Mineral and Metal Processing III*. ECS, Pennington, NJ. pp191-220.

14. Fuerstenau, D.W and Mishra, B.K. (1981), On the mechanisms of pyrite flotation with xanthate as collectors. in M.H. Jones (ed.), *Complex sulfides*. IMM, London, p271-278.
15. Fuerstenau, M.C., (1981), Adsorption of sulphhydryl collectors. In R.P. King (ed), *Principles of Flotation*, pp91-108.
16. Trahar, W. (1983), The influence of pulp potential on sulfide flotation. in M.H. Jones and J.T. Woodcock (editors), *Principles of Mineral Flotation*. AusIMM. pp117-135.
17. Ahlberg, E., Forssberg, E. and Wang, X.H., (1990), Surface oxidation of pyrite in alkaline solution, *Journal of Applied Electrochemistry*, Vol.20, pp1033-1039.
18. Wang, X.H. and Forssberg, (1990) EDTA Induced flotation of sulfide minerals. *Journal of Colloid and Interface Science*, Vol.140, pp217-226.
19. Wang, X.H., Forssner, E. and Ahlberg, E. [1992], Electrochemical studies of the arsenopyrite surface oxidation and collectorless flotation. *J. Appl. Electrochem.* Vol.
20. Wang, X.H., Jiang, C.L., Raichur, A.M., Parekh B.K. and Leonard, J.W., (1992), Comparative studies of surface properties of pyrites from ore and coal sources. in P.E. Richardson and R. Woods (eds.), *Electrochemistry in Mineral and Metal Processing III*. ECS, Pennington, NJ, pp410-432.

Fig.1 Cyclic voltammograms of pyrite at pH=9.2 in KClO₄ electrolyte solutions in the absence and presence of various concentrations of borate as a pH buffer.

Fig.2 Cyclic voltammograms of pyrite at pH=9.4 in NaNO₃ electrolyte solution in the absence and presence of 1×10^{-3} M borate as pH buffer.

Fig.3 Cyclic voltammograms of pyrite at pH=9.4 in 0.1 M sodium perchlorate and in 0.1 M sodium borate electrolyte solutions, respectively.

Fig. 4 Cyclic voltammograms of pyrite at pH=9.2 in potassium perchlorate electrolyte solution in the presence of 1×10^{-3} M sodium borate as pH buffer at different rotation speeds.

Fig.5 Limiting current density of pyrite as a function of the square root rotation speed at pH=9.2 in the presence of 1×10⁻³ M sodium borate.

Fig.6 Concentration-pH distribution diagrams for the borate-water system at total borate concentration (a) 1×10^{-3} M and (b) 0.1 M.

Fig.7 Concentration-pH distribution diagrams of the iron-borate system at total iron concentration of $1 \times 10^{-4} \text{ M}$ and total borate concentration of (a) 0.0 M and (b) 0.1 M.

Fig.8 Concentration-pH distribution diagrams of the iron-borate system at a total iron concentration of $1 \times 10^{-3} \text{ M}$ and total borate concentration of (a) 0.0 M and (b) 0.10 M .

Fig.9 Typical Nyquist plots for pyrite in the absence and presence of $1 \times 10^{-3} \text{ M}$ sodium borate as pH buffer, and at stationary and rotation (1000 RPM).

Fig.10 Typical cyclic voltammograms of galena electrode at pH=9.4 in 0.1 M sodium perchlorate and sodium borate electrolyte solutions.

Fig.11 Cyclic voltammograms of pyrite in sodium perchlorate electrolyte solution at pH=9.2 in the absence and presence of 1×10^{-3} M sodium ethyl xanthate.

Fig.12 Cyclic voltammograms of pyrite in sodium perchlorate solutions at pH=9.2 in the presence of 1×10^{-3} M sodium ethyl xanthate at various rotation speeds.

Fig.13 Linear sweep voltammograms of pyrite and platinum in sodium perchlorate solution in the presence of 1×10⁻³ M sodium ethyl xanthate.

Fig. 14, Cyclic voltammograms of pyrite in sodium perchlorate electrolyte solution at pH=9.2 in the presence of 1x10⁻³ sodium ethylxanthate with and without 1x10⁻³ M sodium borate as pH buffer.

Fig. 15 Cyclic voltammograms of pyrite in 0.1 M sodium borate electrolyte solution (pH=9.4) in the absence and presence of sodium ethylxanthate.

END

DATE
FILMED

5 / 17 / 93