DOE/PC/92106--T1
2

DOE/PC/92106--T1

DE93 013604

DE-AC 22 92 PC 92106

Technical Progress Report

First Quarter: Period Oct. 01, 1992 - Dec. 31, 1992

Charge Distribution Analysis of Catalysts under Simulated Reaction Conditions

Friedemann Freund

Principal Investigator

SURFACE/INTERFACE, Inc.

110 Pioneer Way, Suite D

Mountain View, CA 94041

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Charge Distribution Analysis (CDA) is a technique to measure mobile charge carriers in dielectric materials. CDA is based on the dielectric polarization in an electric field gradient. The measurements are performed contact-free under minimum perturbation conditions at 0 Hertz. The measured physical parameter is the force $F^\pm$ experienced by the sample in an electric field gradient of reversible polarity. CDA allows to determine the sign of the majority charge carriers and the density of surface charges which is correlated to the chemical or catalytic activity. A microbalance is used as a force-sensing device. CDA is particularly well suited to be applied to catalysts and can be used in inert or reactive gas environments.

Fig. 1 shows the block diagram of the system to be build under this Contract. It consists of a modified PERKIN-ELMER TGS-2 microbalance, attached to a newly designed stainless steel sample chamber set into a steel frame with level control and vibration damping devices. The sample chamber contains multiple ports and a new set of furnaces. The TGS-2 microbalance has its own control which allows to select different sensitivity ranges down to 1 μg full scale. A new central control unit will be set up consisting of an APPLE Macintosh computer with a 16" color monitor, the NATIONAL INSTRUMENT LabView[®] data acquisition software, a GPIB (General Purpose Interface Board) and a series of I/O (Input/Output) modules.

Fig. 1: Block diagram of the new CDA apparatus currently under construction

Fig. 2 shows the schematic view of the sample chamber as currently under construction. The basic chamber has a 6" diameter. It features on the front side a hinged, O-ring sealed, quick-release door with a Pyrex® window and on the back side a fixed O-ring sealed Pyrex® window flange. In addition the main chamber has 2 1/2" flanges on the top and the bottom, designed to attach to the TGS-2 balance housing and to accept the micrometer-driven linear motion z-drive for the bias electrode and the recording thermocouple, respectively. Six microflanges (1 3/4" diameter) are arranged around its periphery to accept the various feedthroughs needed to the operation. The two 1 3/4" flanges in the horizontal plane will accept the two halves of the newly designed furnace, mounted on motorized linear motion drives. Also indicated in Fig. 2 are the position of the sample which hangs down from the TGS-2 microbalance and sits on a thin-wire stirrup and the tube which will contain the bias electrode and the recording thermocouple, both mounted on the z-drive.

Fig. 2: Cross section through the main sample chamber

Fig. 3 illustrates the progress made in the theoretical modeling of the CDA response. Using MATLAB software we have modeled the geometry of the asymmetrical capacitor consisting of a circular Au bias electrode (2–3 mm diameter) and a grounded cylindrical Au counterelectrode (10–20 mm diameter, 10–20 mm high). Fig. 3 shows this asymmetrical capacitor in cross section. The left panel depicts the equipotential lines for an electric field of 100 V without a sample. The right panel depicts the equipotential lines for an electric field of 100 V with a homogeneous, ideally dielectric sample with a dielectric constant of 10. The calculations illustrate how the electric field is being pushed out of the sample volume. The force to be measured for an ideally dielectric sample can then be calculated from the computed electric field gradient over the volume of the sample. Such calculations are important for calibrating the new instrument and testing its performance.

Fig. 3: Equipotential field lines calculated for a given sample geometry in the CDA cell

Summary

The first quarter was used to design, build and set up part of the hardware and to initiate the software to be used in the experiments described in the Proposal. The main sample chamber was built, assembled. The steel frame was received. Theoretical work has produced first results. In general, our work has progressed on time with no significant deviations from the planned schedule. No experimental data are yet to report.

A handwritten signature in cursive script, reading "Friedemann Freund". The signature is written in black ink and is positioned above the printed name.

Friedemann Freund, P.I.

Jan. 30, 1993

END

**DATE
FILMED**

6 / 10 / 93