Methane Oxidation Over Dual Redox Catalysts

Final Report

**Kamil Klier
Richard G. Herman
Zbigniew Sojka
Juana Isabel DiCosimo
Stefaan DeTavernier**

Work Performed Under Contract No.: DE-FG21-89MC26039

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Lehigh University
Zettlemoyer Center for Surface Studies
Bethlehem, Pennsylvania 18015**

June 1992

TABLE OF CONTENTS

Disclaimer	ii
TABLE OF CONTENTS	iii
SUMMARY	1
 I. CATALYTIC SYSTEMS BASED ON ZINC OXIDE - SELECTIVITY SWITCH FROM C ₂ HYDROCARBONS TO FORMALDEHYDE	4
I-1. Preparation and Testing of Cu-, Fe-, Cu/Fe-, and Cu/Sn- doped Zinc Oxide Catalysts	4
Catalyst Preparations	4
Experimental Testing Results - Binary Doped Catalysts	8
Methane Oxidation Over Cu/ZnO and Fe/ZnO Catalysts	21
Summary	31
I-2. Characterization of the ZnO, Cu/ZnO, Fe/ZnO and Cu/Fe/ZnO Catalysts	34
Phase Analysis	34
Catalyst Surface Area, Particle Sizes, and Microstructure	34
XPS Surface Analysis of the ZnO, Cu/ZnO, Fe/ZnO and Cu/Fe/ZnO Catalysts	38
Surface Composition	40
Surface Chemical State Analysis of Cu and/or Fe Doped ZnO	44
 II. CATALYTIC SYSTEMS BASED ON Cu, Fe-DOPED ZSM-5 ZEOLITE ..	51
II-1. Preparation of CuFe-ZSM-5 Zeolite	51
II-2. Catalyst Testing	55
II-3. Summary	64
 III. METHANE OXIDATION OVER PALLADIUM-BASED CATALYSTS ..	65
III-1. Preparation, Characterization and Testing of Palladium-Based Catalysts	65

Catalyst Preparation	65
Characterization	66
Catalytic Testing of the Catalyst	67
III-2. METHANE OXIDATION OVER Pd-DOPED Cu/Fe/ZnO CATALYSTS	68
Catalyst Preparation and Characterization	68
Catalytic Testing of the Catalysts	74
III-3. FURTHER EFFECTS OF Pd LOADING IN Pd-SiO₂ CATALYSTS	89
Catalyst Preparation	89
Catalyst Activation	90
Catalyst Characterization	91
Catalytic Testing	94
Treatment with Halogenated Promoter	95
Effect of Pd doping	95
Effect of CH ₄ /O ₂ Ratio	95
Conclusions	104
III-4. Summary	104
IV. OXIDATIVE COUPLING OF METHANE OVER Fe, Sn, Bi, AND Sb-DOPED STRONTIUM-LANTHANA CATALYSTS	106
IV-1. Preparation, Characterization, and Testing of the FeO_x/SrO/La₂O₃ Catalyst	106
Preparation of Fe ³⁺ Doped Sr/La ₂ O ₃ Catalyst	106
Catalyst Characterization	107
Catalytic Tests	111
Sr/La ₂ O ₃	111
Fe/Sr/La ₂ O ₃	120
Conclusions	127
IV-2. Preparation, Characterization, and Testing of the SbO_x/SrO/La₂O₃, BiO_x/SrO/La₂O₃, and SnO_x/SrO/La₂O₃ Catalysts	127
Preparation and Characterization	127
Catalytic Testing	128
Summary	131
REFERENCES	134

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

SUMMARY

Catalytic oxidation of methane to partial oxidation products, primarily formaldehyde and C₂ hydrocarbons, was found to be directed by the catalyst used. In this project, it was discovered that a moderate oxidative coupling catalyst for C₂ hydrocarbons, zinc oxide, is modified by addition of small amounts of Cu and Fe dopants to yield fair yields of formaldehyde. A similar effect was observed with Cu/Sn/ZnO catalysts, and the presence of a redox Lewis acid, Fe^{III} or Sn^{IV}, was found to be essential for the selectivity switch from C₂ coupling products to formaldehyde. The principle of double doping with an oxygen activator (Cu) and the redox Lewis acid (Fe, Sn) was pursued further by synthesizing and testing the CuFe-ZSM-5 zeolite catalyst. The Cu^{II}(ion exchanged) Fe^{III}(framework)-ZSM-5 also displayed activity for formaldehyde synthesis, with space time yields exceeding 100 g/h-kg catalyst. However, the selectivity was low and earlier claims in the literature of selective oxidation of methane to methanol over CuFe-ZSM-5 were not reproduced. Both the doubly doped ZnO and the ZSM-5 catalysts were characterized, to the degree deemed necessary, by X-ray diffraction, compositional analysis, surface analysis, surface area measurements, and surface valence state determination of the dopant elements.

In an effort to lower the temperature of methane activation, supported palladium metal was explored first as a catalyst of its own merit (Pd/SiO₂) and then as a co-dopant of the Cu/Fe/ZnO oxide catalyst. In all cases, the addition of Pd resulted in a very significant increase of activity but simultaneously a decrease of selectivity due to enhancement of complete combustion of methane. The Pd particles were found to be in

the size range of 8.5-22 nm, which was larger than intended by the preparation methods. Based on the results with this "normal" Pd dispersion, it is evident that the metal dispersion must be increased to achieve satisfactory selectivities. Ultrafine effective dispersions are achieved with large particles by "ensemble-controlling" modifiers such as halogens or by preparing very stable dispersions on special supports. The first goal was attempted by pre-doping the Pd/SiO₂ catalysts by CH₂Cl₂ but surface analysis detected no chlorine on the surface, indicating that a continuous flow of CH₂Cl₂ would have to be used. This would complicate the analysis of testing results by having to resolve gas phase free radical and surface reactions, a research outside the scope of this project. Therefore, a search for other than halogen ensemble controlling agents has been initiated under a parallel AMOCO-sponsored project. The very fine, sub-nanometer Pd dispersions are also achievable using special support and calcination procedures based on some very recent patent literature. It is believed that ultra-fine dispersions of Pd metal supported on oxides do have the potential to catalyze selective oxidations of methane at lower temperatures, and therefore research along these lines is worth pursuing further. This is of interest to our industrial partner, AMOCO, who will continue supporting our work on methane conversions over metals.

The most significant results were obtained in the latest stages of the report period. When studying a new oxide system, SrO/La₂O₃, for the effects of surface modifiers on methane conversions, it was discovered that surface doping with 0.5% of the oxides of elements in the right lower portion of periodic table, viz. Sb, Bi, and Sn, the C₂ coupling rates were enhanced to the degree that the oxidative coupling of methane could be carried out at commercially attractive temperatures of 550-600°C, in contrast to the 750-800°C temperature range of activity for the undoped SrO/La₂O₃. At the same time, the unsaturated C₂(ethylene)-to-saturated C₂(ethane) selectivity had increased over the doped

catalysts, yielding 100 mol of ($C_2^* + C_2$)/h-kg cat at 600°C over the most effective $SbO_x/SrO/La_2O_3$ catalyst. With the standard level of 0.5% dopant, the Sb, Bi, and Sn-doped SrO/La_2O_3 catalysts have not yet been optimized and further significant improvements are expected upon optimizing the surface concentration of the dopant elements.

In conclusion, (i) a new active and selective catalytic system ($M = Sb, Bi, Sn$)/ SrO/La_2O_3 has been discovered for potentially commercially attractive process for the conversion of methane to C_2 hydrocarbons, (ii) a new principle has been demonstrated for selectivity switching from C_2 hydrocarbon products to formaldehyde in methane oxidations over Cu, Fe-doped zinc oxide and ZSM-5, and (iii) a new approach has been initiated for using ultrafine metal dispersions for low temperature activation of methane for selective conversions. Item (iii) continues being supported by AMOCO while further developments related to items (i) and (ii) are the objective of our continued effort under the METC-AMOCO proposed joint program.

METHANE OXIDATION OVER DUAL REDOX CATALYSIS

I. CATALYTIC SYSTEMS BASED ON ZINC OXIDE - SELECTIVITY SWITCH FROM C₂ HYDROCARBONS TO FORMALDEHYDE

The objective of this research was to develop new approaches to the direct selective catalytic oxidation of methane over oxides that are doubly doped with a redox couple, such as Cu⁺/Cu²⁺ and another dopant that executes both a redox and Lewis acid/base function, e.g. Fe²⁺/Fe³⁺ or Sn³⁺/Sn⁴⁺. The desired process aims at employing one redox couple for activation of oxygen and another for the trapping of methyl radicals. The ·CH₃ species can either recombine to give C₂ hydrocarbons or be converted via electron transfer with the second redox couple to give transient carbocations, which can react with surface OH⁻ groups to form oxygenates. Subsequent electron exchange between the couples, made possible by the close balance of their redox potentials, closes the catalytic cycle. In order to establish the foundations of such a process the dual redox Cu⁺/Fe³⁺/ZnO and Cu⁺/Sn⁴⁺/ZnO catalysts that show promise for the direct synthesis of oxygenates from methane were tested in the 450-850°C temperature range at ambient pressure under continuous flow steady-state conditions.

I-1. Preparation and Testing of Cu-, Fe-, Cu/Fe-, and Cu/Sn- doped Zinc Oxide Catalysts

Catalyst Preparations

The binary doped Cu⁺/Fe³⁺/ZnO catalysts were prepared by firing at 1000°C a mixture composed of Cu₂O, hydrous Fe₂O₃ and of ZnO. The samples were previously treated at 400°C for 2 h in dry and oxygen free nitrogen. The general three-step preparation procedure is depicted in Scheme I: It involves preparation of the starting oxides by precipitation from nitrate solutions and thermal decomposition, two-step mixing of the

SCHEME I

PREPARATION PROCEDURE

oxides by grinding in an alumina mortar, and finally thermal treating the samples according to form solid solutions.

Hydrous iron oxide was obtained by adding 5% NH_4OH (5 ml/min) to a 75.96 g of $\text{Fe}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$ dissolved in 1000 ml of distilled water at 50°C to reach the final pH of 4.13. After washing until no presence of nitrate was detected in the effluent, the reddish brown residue was filtered and dried for three weeks. The actual content of Fe (61.42 %) was determined by titration with 0.01 N KMnO_4 according to the Zimmermann-Reinhard method [3]. This corresponds to the stoichiometric formula of $\text{Fe}_2\text{O}_3 \cdot 1.23\text{H}_2\text{O}$. The phase composition determined by X-ray diffraction shows the presence of hematite (three most intense lines at 2.70, 2.52, 1.67 Å; ASTM card 24-72) and goethite (peaks at 4.18, 2.69, 2.45 Å; ASTM card 17-536) in proportions of 40 and 60%, respectively. Zinc oxide was obtained by thermal decomposition at 350°C for 50 h of hydrozincite prepared as described in [4]. Cuprous oxide was obtained by thermal decomposition of copper hydroxycarbonate at 1050°C and cooling to room temperature in a stream of nitrogen. All oxides were preliminarily ground for 1 h. In order to assure a good dispersion and stoichiometry of the doped zinc oxide catalysts, an equimolar mixture of Cu_2O and $\text{Fe}_2\text{O}_3 \cdot 1.23\text{H}_2\text{O}$ was prepared by grinding 4.2924 g of cuprous oxide with 4.7907 g of hydrous iron oxide for 1 h. Then 1.1576 g of this mixture was intimately mixed for 2 h with 56.8176 g of ZnO until a uniform pale pink powder was obtained. The actual chemical composition of the starting oxide mixture corresponded to $\text{Cu}_{1.02}\text{Fe}_{1.07}\text{Zn}_{97.91}\text{O}$ as determined by atomic absorption spectroscopy. The samples were thermally pretreated in a stream of deoxygenated and water free nitrogen at 400°C for 2 h in a specially constructed Pyrex glass apparatus, which enabled a direct transfer of the samples to attached quartz vessels for further evaluation (2 h) and high temperature treatment. Typically, the samples were fired in closed

evacuated silica vessels for 18 h at 1000°C and for 22 h at 1000°C in evacuated or open to air quartz ampoules. For the sake of simplicity, these samples were labelled as Cu/Fe/ZnO-18v, Cu/Fe/ZnO-22v and Cu/Fe/ZnO-22a, respectively. After the different thermal treatments a change of color was observed; the samples heated at 400°C became pale blue, while those fired at 1000°C in evacuated vessels were black, and those fired in air at 1000°C were gray.

The binary $\text{Fe}^{+3}/\text{ZnO}$ and $\text{Cu}^{+1}/\text{ZnO}$ catalysts were prepared by firing at 1000°C in air a mixture composed of hydrous iron oxide with zinc oxide and of cuprous oxide with ZnO, respectively. The multistep preparation procedure was analogous to that applied for the preparation of doubly doped zinc oxide catalysts, as described in detail in the previous section. It involved preparation of the starting hydrozincite $\text{Zn}_5(\text{OH})_6(\text{CO}_3)_2$ by the addition of 1 M Na_2CO_3 to an aqueous zinc nitrate solution until a pH of 7 was achieved. Hydrous iron oxide was obtained by adding 5% NH_4OH to 1 l of 0.188 M aqueous solution containing $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ at 50°C until a pH of 4.19 was achieved. The latter precipitate was then filtered, washed free of nitrate, and dried to yield $\text{Fe}_2\text{O}_3 \cdot 1.23\text{H}_2\text{O}$ composed of 40% hematite and 60% goethite, as determined by KMnO_4 titration and XRD, respectively. Cu_2O was obtained by thermal decomposition of copper hydroxycarbonate in a stream of nitrogen at 1000°C. All oxides were preliminarily ground for 1 h.

For the preparation of the Fe/ZnO catalyst, 25.0004 g of ZnO was intimately mixed for 2 h with 0.2794 g of $\text{Fe}_2\text{O}_3 \cdot 1.23\text{H}_2\text{O}$ until a uniform pale brown powder was obtained. The Cu/ZnO sample was prepared, according to the same procedure, by mixing 25.0000 g of ZnO with 0.2900 g Cu_2O to obtain a pale pink powder. Subsequently, the Fe/ZnO and Cu/ZnO samples were thermally pretreated in a stream of deoxygenated and water-free nitrogen at 400°C for 2 h in a Pyrex apparatus and then transferred into quartz ampoules

for final heating in air at 1000°C for 22 h. After the different thermal treatments, a change of color was observed. Both samples heated at 400°C became pale blue, while after the firing treatment at 1000°C, the Cu/ZnO sample became light green and the Fe/ZnO sample turned light beige. The actual compositions of the binary catalysts, assuming that zinc oxide non-stoichiometry can be neglected, corresponded to $\text{Fe}_{0.00973}\text{Zn}_{0.99027}\text{O}$ and $\text{Cu}_{0.00997}\text{Zn}_{0.99003}\text{O}$, as determined by atomic absorption spectroscopy.

Experimental Testing Results - Binary Doped Catalysts

The catalysts that were tested initially consisted of the Cu/Fe/ZnO, Cu/Sn/ZnO, and undoped ZnO catalysts that were prepared by firing at 1000°C for 22 h in air as described in detail previously. A 0.114 g portion of each of the catalysts was loaded into the 6 mm OD quartz reactor that narrowed into a 2 mm ID capillary immediately below the catalyst bed to allow rapid product removal. Quartz wool plugs of 0.4-0.5 cm in height below and 2-3 cm above the bed were used to position the catalyst in the reactor. Initial product analyses were achieved by sequential on-line injection into parallel columns consisting of a 3.2 mm x 2 m Porapak Q packed fused silica column (separation of air, CH_4 , C_2H_4 , C_2H_6 , and H_2O) and a 3.2 mmx2 m packed 13X zeolite column (separation of O_2 , N_2 , CH_4 , and CO) in a Hewlett-Packard 5730A chromatograph interfaced with a 5880A integrator. Testing at each temperature was typically carried out for 2.5-3.5 h while carrying out the gas chromatographic analyses every six min. Condensable water-soluble products were collected in two water-filled scrubbers in series, the first was kept at room temperature and the second at 0°C. Formaldehyde was qualitatively detected by the West and Sen chromotropic acid method [1] and was quantitatively determined by the modified Romijn's iodometric titration [2]. The ultra-high purity methane (99.97%) and zero-grade air (synthetic O_2/N_2 mixture) reactants were obtained from Air Products and Chemical, Inc. Testing was carried

out at ambient pressure with a reactant mixture of methane/air = 1:1 with gas hourly space velocity (GHSV) = 70,000 ℓ /kg catal/h in the temperature range of 450-850°C. Three independent runs were performed for each of the catalyst.

Appreciable conversion of reactants was noted at 450°C, and more than 90% of the oxygen was consumed at 750°C and 800°C for the Cu/Sn/ZnO and Cu/Fe/ZnO catalysts, respectively (Figure 1). However, for pure ZnO even at the highest temperatures, the oxygen conversion was still below 65%. The associated temperature dependence of methane conversion, as shown in Figure 2, reached the maximum value of about 15% at 850°C for all three catalysts. A rapid increase of O₂ and CH₄ conversions at 750°C for tin- and at 800°C for iron-containing catalysts was observed together with the deposition of the coke on the catalysts at those temperatures.

The principal products detected during these studies were CO₂, CH₂O, CO with small amounts of H₂ (not quantified), and C₂ coupling products, as well as water. The temperature dependences of the formation of these products over all three catalysts are presented in Figure 3-5.

Two main temperature regions could be distinguished with respect to the performance of the catalysts. One region occurred below 700°C with formaldehyde as a principal partial oxidation product, and a second region was observed above 750°C which gave mainly C₂ coupling products together with CO. In Figures 6 and 7, the selectivities to formaldehyde and C₂H_n (n = 4,6) are presented. As implied by Figure 6, the selectivities toward CH₂O are much different over the three catalysts. Those catalysts that were doped with Cu and Fe or Sn exhibited significant improvement in the CH₂O selectivity in comparison to the pure zinc oxide. For example, at 600°C the Cu/Fe/ZnO, Cu/Sn/ZnO, and ZnO catalysts showed 25.3, 13.7, and 2.5 carbon atom% CH₂O selectivities, respectively,

OXYGEN CONVERSION

$\text{CH}_4/\text{AIR} = 1.0$, GHSV = 70,000 l/kg cat/h

FIGURE 1

METHANE CONVERSION

$\text{CH}_4/\text{AIR} = 1.0$, GHSV = 70,000 l/kg cat/h

FIGURE 2

YIELDS OF PRODUCTS OVER Cu/Fe/ZnO

CH₄/Air = 1.0, 0.114 g Catalyst

GHSV = 70,000 l/kg catal/h

FIGURE 3

YIELDS OF PRODUCTS OVER Cu/Sn/ZnO

CH₄/Air = 1.0, 0.114 g Catalyst

GHSV = 70,000 l/kg catal/h

FIGURE 4

YIELDS OF PRODUCTS OVER ZnO

$\text{CH}_4/\text{Air} = 1.0, 0.114 \text{ g Catalyst}$

$\text{GHSV} = 70,000 \text{ l/kg catal/h}$

FIGURE 5

SELECTIVITY TO FORMALDEHYDE

FIGURE 6

SELECTIVITY TO C₂ PRODUCTS

FIGURE 7

while the remainder of the product was CO_2 . The simultaneous decrease of associated CO_2 selectivity in this temperature region (Figure 8) indicates that the dopants depressed the ZnO activity for deep oxidation to form CO_2 and promoted the formation of formaldehyde. As the temperature was increased to 650°C and above, the CH_2O selectivities decreased, but the space times yields significantly increased, as shown in Figure 9. In the high temperature range, i.e. $> 700^\circ\text{C}$, the activity of the ZnO catalyst uniformly increased, and the decrease in the selectivity toward CH_2O (Figure 6) was due to the significant increase in the yield and selectivity of the C_2 products (Figure 7). For example, at 800°C the CH_2O and CO selectivities were <0.5 and 5.5 carbon atom%, respectively, while the dominant products over the single component ZnO catalysts were C_2H_n and CO_2 with selectivities of 46.6 and 47.5 carbon atom%, respectively.

Over the Cu/Sn/ZnO catalyst, the activity and CH_2O space time yield reached maxima at 750°C , and the products consisted of CH_2O (1.4 carbon atom%), CO_2 , and only small amounts of C_2 species. Increasing the temperature of the Cu/Sn/ZnO catalyst to 800°C did not increase the yield of CH_2O but did increase the yield of all of the other products, e.g. an appreciable quantity of the C_2 coupling product was observed, and the selectivities to CH_2O , CO , C_2H_n , and CO_2 were 0.53 , 4.8 , 9.8 , 84.9 carbon atom%, respectively. At temperatures of 750 - 800°C , deposition of coke on the catalyst occurred.

At 700°C , the Cu/Fe/ZnO catalyst exhibited a 14.2 carbon atom% selectivity for CH_2O with only 2.3 carbon atom% of the C_2 products present. However, this catalyst did not exhibit a maximum in formaldehyde yield until 750°C , see Figure 9, where the CH_2O , CO , C_2H_n , and CO_2 selectivities were 9.4 , 3.3 , 5.2 , and 82.3 carbon atom%, respectively. At that temperature, a space time yield of 76 g CH_2O /kg catal/h was observed. At 800 - 850°C , a deactivation toward CH_2O was noted for both Cu/Fe- and Cu/Sn-doped catalysts, while

SELECTIVITY TO CO₂

FIGURE 8

CH₂O SPACE TIME YIELD

FIGURE 9

the yield of C₂ products increased greatly. However, the C₂ selectivity was still only 20-40% of that observed over the pure ZnO catalyst at these temperatures (Figure 7). A comparison of the selectivities to C₂ hydrocarbons with the selectivities to formaldehyde (Figure 6 and 7) for pure and doped zinc oxide indicates that the Cu/Sn and especially the Cu/Fe dopants shift the selectivity from C₂ coupling products toward CH₂O. In addition, as revealed by Figure 8, they also depress the ZnO activity to CO₂ formation in the <700°C temperature region.

Methane Oxidation Over Cu/ZnO and Fe/ZnO Catalysts

Testing of these catalysts was carried out with a 0.114 g portion of air-fired catalysts loaded into the 6 mm OD quartz reactor as described in the previous section of this report. Four independent runs were performed for each of the catalysts. For the sake of comparison, these catalytic test results are presented along with the data for the pure ZnO.

At 450-500°C, the conversion of reactants was negligible and only traces of CH₂O and CO₂ could be detected. An appreciable conversion of reactants was noted above 550°C, and more than 60% of the oxygen was consumed at 850°C for the Cu/ZnO catalyst, which was similar to the pure ZnO (Figure 10). However, the oxygen conversion was still below 32% for the Fe/ZnO catalyst even at the highest temperatures. The associated temperature dependence of methane conversion, as shown in Figure 11, reached the maximum value of about 7% at 350°C for Fe/ZnO and 10% for Cu/ZnO catalysts. The relatively high conversion of methane in the case of Fe/ZnO catalysts with respect to the associated oxygen conversion in comparison to the Cu/ZnO sample is caused by its high C₂ selectivity. In contrast to the ternary Cu/Fe/ZnO catalyst, no rapid increase of O₂ and CH₄ conversions at 800°C for Cu-containing catalyst was observed despite the deposition of coke on the catalysts at this temperature.

As in the case of doubly doped catalysts, the principal products detected during these studies were CO₂, CH₂O, and CO with small amounts of H₂ (not quantified), and C₂ coupling products, as well as water. The temperature dependences of the formation of the carbon-containing products over Fe/ZnO and Cu/ZnO catalysts are presented in Figures 12 and 13.

Two main temperature regions can be distinguished with respect to the performance of the catalysts. One region occurred below 700°C with formaldehyde as a principal partial

OXYGEN CONVERSION

$\text{CH}_4/\text{AIR} = 1.0$, $\text{GHSV} = 70,000 \text{ l/kg cat/h}$

FIGURE 10

METHANE CONVERSION

$\text{CH}_4/\text{AIR} = 1.0$, GHSV = 70,000 l/kg cat/h

FIGURE 11

YIELDS OF PRODUCTS OVER Fe/ZnO

CH₄/Air = 1.0, 0.114 g Catalyst

GHSV = 70,000 l/kg catal/h

FIGURE 12

YIELDS OF PRODUCTS OVER Cu/ZnO

CH₄/Air = 1.0, 0.114 g Catalyst

GHSV = 70,000 l/kg catal/h

FIGURE 13

oxidation product, and a second region was observed above 750°C where mainly C₂ coupling products together with CO were formed. In Figures 14 and 15, the selectivities (carbon atom%) to formaldehyde and C₂H_n (n = 4,6) are presented. As implied by Figure 14, the selectivities toward CH₂O are much different over the two catalysts. The Fe doped catalyst exhibited significant improvement in the CH₂O selectivity in comparison to the pure zinc oxide, while for Cu/ZnO catalyst a notably smaller increase of formaldehyde selectivity was observed. For example, at 600°C the Fe/ZnO, Cu/ZnO, and ZnO catalysts showed 76.3, 28.7, and 2.5 carbon atom% CH₂O selectivities, respectively, while the remainder of the product was CO₂. The simultaneous decrease of associated CO₂ selectivity in this temperature region (Figure 16) indicates that the dopants depress the ZnO activity for deep oxidation to form CO₂ and promote the formation of formaldehyde.

As the temperature was increased to 650°C and above, the CH₂O selectivities decreased, but the space times yields significantly increased, as shown in Figure 17. In the high temperature range, i.e. > 700°C, the activity of the Cu/ZnO catalyst increased and the decrease in the selectivity toward CH₂O (Figure 14) was due to the significant increase in the yield and selectivity of the complete oxidation product CO₂ and to a lesser extent the C₂ products (Figure 15 and 16). For example, at 850°C where the yield of the CH₂O reached its maximum over the Cu/ZnO catalyst, the CH₂O and CO selectivities were 1.5 and 20.9 carbon atom% respectively, while the dominant products were CO₂ and C₂H_n with selectivities of 40.9 and 36.5 carbon atom%, respectively. The latter value was about 1/3 less than that observed for pure ZnO. At temperatures of 750-800°C, deposition of coke on the catalysts occurred.

At 700°C, the Fe/ZnO catalyst exhibited a 45.5 carbon atom% selectivity for CH₂O with only 10.1 carbon atom% of the C₂ products present. However, this catalyst did not

SELECTIVITY TO FORMALDEHYDE

FIGURE 14

SELECTIVITY TO C₂ PRODUCTS

FIGURE 15

SELECTIVITY TO CO₂

FIGURE 16

CH₂O SPACE TIME YIELD

FIGURE 17

exhibit a maximum in formaldehyde yield until 800°C, see Figure 17, where the CH₂O, CO, C₂H_n, and CO₂ selectivities were 8.0, 16.6, 47.3, and 31.7 carbon atom%, respectively. At that temperature, a space time yield of 77.8 g CH₂O/kg catal/h was observed. At the higher temperature of 850°C, a slight deactivation toward CH₂O was noted for the Fe-doped catalyst. The yield of C₂ products increased greatly above 750°C over the Fe/ZnO catalyst with C₂ selectivity close to that observed over the pure ZnO catalyst at these temperatures (Figure 15). A comparison of the selectivities to C₂ hydrocarbons with the selectivities to formaldehyde (Figure 14 and 15) for pure and doped zinc oxide indicates that the Fe largely, and to much less extent also Cu dopant, improved the selectivity toward CH₂O formation. However, while the C₂ selectivity of the Fe/ZnO catalyst remained at the same level as for pure ZnO, for Cu/ZnO catalysts it was distinctly smaller and approached maximally 60% of the ZnO values. In addition, as revealed by Figure 16, the Fe ions also significantly suppressed the ZnO activity toward CO₂ formation in the whole temperature range.

Summary

The doubly doped Cu⁺/Fe³⁺/ZnO and Cu⁺/Sn⁴⁺/ZnO catalysts having compositions of Cu_{0.010}Fe_{0.011}ZnO_{0.979}O and Cu_{0.010}Sn_{0.005}ZnO_{0.985}O, as well as undoped ZnO catalysts, were successfully tested under continuous flow steady-state conditions for methane conversion to oxygenates and C₂ coupling products from a CH₄/air = 1/1 reactant with GHSV = 70,000 l/g catal/h at 450-850°C and ambient pressure. These are reaction conditions expected to yield partial oxidation products over this type of catalyst, but the conditions have not yet been optimized in any way. Appreciable methane conversion occurred at temperatures of 450°C to 700°C with formaldehyde and carbon dioxide as the oxidation products. In the range of 800-850°C, the methane coupling reaction dominated,

especially for undoped ZnO, and formation of both C_2H_4 and C_2H_6 was observed together with CO_2 , $CO + H_2$ and small amounts of CH_2O .

Addition of the redox metal ion dopants to the ZnO matrix significantly promoted the catalytic conversion of methane to *formaldehyde* at the designated reaction conditions, giving the maximum space time yield of 76 g/kg catal/h for the Cu/Fe/ZnO catalyst at 750°C. It has been shown that the Cu/Fe and Cu/Sn dopants also *shift the selectivity* from C_2 coupling products toward formaldehyde and, at temperatures below 650°C, suppress the activity toward the deep oxidation reaction that yields CO_2 .

Singly doped Fe^{3+}/ZnO and Cu^+/ZnO catalysts, having compositions of $Fe_{0.0097}Zn_{0.9903}O$ and $Cu_{0.0097}Zn_{0.9903}O$, were synthesized and successfully tested under continuous flow steady-state conditions for methane conversion to oxygenates and C_2 coupling products from a $CH_4/air = 1/1$ reactant feed with GHSV = 70,000 l/g catal/h at 450-850°C and ambient pressure. These are reaction conditions identical to those previously used for doubly doped Cu/Fe/ZnO, Cu/Sn/ZnO, and ZnO catalysts, and they yielded the same partial oxidation products over the singly doped catalysts. Appreciable methane conversion occurred at temperatures of 550°C to 700°C, with formaldehyde and carbon dioxide as the oxygen-containing products. In the range of 800-850°C, the methane coupling reaction dominated, especially for iron-doped ZnO, and formation of both C_2H_4 and C_2H_6 was observed together with CO_2 , $CO + H_2$, and relatively large amounts of CH_2O .

Addition of the redox Fe cation dopant to the ZnO matrix significantly promoted the catalytic conversion of methane to formaldehyde at the designated reaction condition, via a large increase of the CH_2O selectivity, giving the maximum space time yield of 77.8 g/kg catal/h at 800°C. However, a pronounced decrease of the overall activity of the Fe/ZnO

catalyst, in comparison to the pure zinc oxide, was also observed. In contrast to the doubly doped Cu/Fe/ZnO catalyst, the single Fe dopant caused no apparent shift in the selectivity from C₂ coupling products toward formaldehyde, since there was a high selectivity for C₂ products at high temperature that was approximately the same as for the ZnO catalyst. A feature of the single Fe dopant was a sharp decrease of the activity toward the deep oxidation reaction that yields CO₂, which corresponded to the enhancement in CH₂O selectivity.

The single copper dopant, in comparison to the iron dopant, showed lower CH₂O, CO, and C₂ selectivities and much higher CO₂ selectivity. However, the total activity of the Cu/ZnO catalyst was greater than that of the Fe/ZnO catalyst. Above 650°C, the Cu/ZnO catalyst, relative to ZnO, exhibited a shift in selectivity from C₂ products to CO₂. The Cu/ZnO material also catalyzed a severe deposition of coke at temperatures of 750-800°C.

I-2. Characterization of the ZnO, Cu/ZnO, Fe/ZnO and Cu/Fe/ZnO Catalysts.

The CuZnO, Fe/ZnO, Cu/Fe/ZnO, as well as the base undoped ZnO, catalysts have been fully characterized in terms of morphology, surface area, bulk and surface compositions, and chemical states of the dopants. By high resolution X-ray photoelectron spectroscopy (HR-XPS), it is shown that surface enrichment of the ZnO occurs by Cu-Fe pairs and that the Cu is present as tetrahedral Cu^+ . Although the exact symmetry and oxidation state of the Fe could not be firmly established, it is proposed that the ion pairs exist as $\text{Cu}^+-\text{Fe}^{3+}$ in tetrahedral surface sites.

Phase Analysis

The newly synthesized Fe/ZnO and Cu/ZnO catalyst that had been successfully prepared and tested for the selective oxidation of methane to formaldehyde were routinely examined for crystallinity and phase integrity by X-ray powder diffraction (XRD).

The XRD patterns were recorded in the $30\text{-}150^\circ$ (2θ) range with a Philips diffractometer using CuK_α radiation. In Figure 18, typical diffraction patterns of Fe-doped (Figure 18a) and Cu-doped (Figure 18b) ZnO obtained by firing at 1000°C for 22 h in air are presented. The patterns show distinct lines as listed in ASTM card No. 5-0664 that conform with a hexagonal lattice of zinc oxide. Neither in the case of the Cu/ZnO nor the Fe/ZnO catalyst were other diffraction peaks observed, indicating the formation of true solid solutions. The width of the diffraction lines was close to the instrumental broadening, revealing high crystallinity of both of these samples.

Catalyst Surface Area, Particle Sizes, and Microstructure.

The influence of thermal treatment and doping on the surface area, particle sizes, and micromorphology of the synthesized catalysts was studied by a Quantasorb surface area analyser (Quantachrome Corporation, Model OS-9) with corroboration of scanning electron

microscopy using a Cambridge Stereoscan 150 Instrument. For the determination of surface areas, typically about 1 g of sample outgassed at 250°C prior to N₂ admission was used for the measurements. The SEM samples were dispersed on double-stick tape on an aluminum holder and coated with 150 Å thin Au/Pd film by vacuum evaporation. The scanning electron micrographs of the Fe/ZnO and Cu/ZnO catalysts revealed the presence of randomly aggregated crystallites with rather uniform dimensions and blunt confined shapes (Figures 19a and 19b), indicating that sintering of doped zinc oxide catalysts resulted in the coarsening of particles without significant densification. The distinct differences observed in the micromorphologies and particle shapes were dependent on doping. Generally, the Cu/ZnO catalyst showed larger crystallite dimensions, with more uniform size and shape, than those doped with iron (Figure 19). The Fe/ZnO catalyst tended to form a looser structure with more interparticle voids in comparison to the Cu/ZnO sample that formed more compact aggregates. The Cu/ZnO sample sintered in air exhibited large, fairly uniform, round crystallites typical of the final state of coalescence (Figure 19b), while the Fe doped sample showed a broader distribution of grain sizes (Figure 19a). In the latter case, the particles were interconnected by relatively thin necks forming aggregate structures composed of several smaller crystallites. However, in Cu/ZnO samples the neck growth in the contact area between particles was more developed, resulting in the final stages of the grain boundaries migration away from the contact plane and relatively large clustered grains were formed. This indicates that Cu facilitated the sintering of zinc oxide to a far greater extent in comparison to Fe dopant.

Similar sintering behavior, i.e. coarsening of particles without appreciable structure densification, was also observed for pure ZnO and the doubly doped Cu/(Fe or Sn)/ZnO catalysts. The Cu/Fe/ZnO catalysts tended to form a looser structure with more

FIGURE 19

a
Fe/ZnO

2 μ

b
Cu/ZnO

interparticle voids in comparison to the Cu/Sn/ZnO samples that formed more compact aggregates. The observed sintering behavior is fully accounted for by Greskovich-Lay mechanism of sintering [5]. This mechanism involves the growth of a neck between two particles and subsequent migration of the boundary followed by spheridization of the remaining single particle. This results in larger grains engulfing neighboring smaller ones, forming in intermediate stages, clusters of particles whose size and shape depend on the initial particle size and number of mutual contacts.

The distribution of particle sizes is presented in Figures 20a and 20b for Fe/ZnO and Cu/ZnO samples, respectively. The average particle sizes varied from 0.7-1.5 μm for Fe/ZnO to 2-3 μm for Cu/ZnO, in comparison to 1-1.5 μm for the pure ZnO 2 μm for Cu/Fe/ZnO, and 1.5 μm for Cu/Sn/ZnO catalysts fired in air. The surface areas of 0.6 m^2/g for Fe/ZnO and 0.2 m^2/g for Cu/ZnO were obtained. These values correspond to mean values of spherical particles having diameters in the range of 2-5 μm , in agreement with the SEM micrographs. Bet surface areas of 0.45-0.50 m^2/g for pure ZnO, 0.30-0.35 m^2/g for (Cu/Fe)-doped, and 0.25-0.30 for (Cu/Sn)-doped samples fired at 22 h were obtained.

XPS Surface Analysis of the ZnO, Cu/ZnO, Fe/ZnO and Cu/Fe/ZnO Catalysts.

The surface analyses of ZnO, Cu/ZnO, Fe/ZnO, and Cu/Fe/ZnO catalysts were carried out using a SCIENTA ESCA-300 X-Ray Photoelectron Spectrometer (XPS) equipped with a rotating anode X-ray source (Al K_{α} , $h\nu = 1486.6 \text{ eV}$), double focusing X-ray monochromator, hemispherical photoelectron analyser, and computer controlled instrument operation and data acquisition system. A Submonolayer Science flood gun was used for charge neutralization of the samples. The survey scans were recorded in the binding energy range of 0-1050 eV with a pass energy 300 eV. For quantitative analysis, 20-40 eV

FIGURE 20

PARTICLE SIZE DISTRIBUTION for Fe/ZnO catalyst

for Cu/ZnO catalyst

scans were taken with a pass energy of 75 eV. The typical background pressure was better than 10^{-9} Torr. The spectral smoothing, deconvolution, and integration was performed using a software package provided by SCIENTA. The peak positions were calibrated relative to the Zn $2p_{3/2}$ (BE = 1021.7 eV) and adventitious carbon 1s line (BE = 285 eV [6]). In order to reduce the differential charging of the samples, revealed by preliminary experiments to be significant, and possible contamination of the catalysts by contact with the ambient atmosphere, the following procedure for sample preparation was employed. After firing at 1000°C, the catalysts were sealed at that temperature in quartz ampoules and transferred to a glove-bag filled with dry oxygen-free nitrogen. The catalyst powder was pressed into indium foil, which was then attached by means of a drop of gallium to a glass plate. The entire assembly was then held to the stainless steel sample holder with beryllium brass clips, as shown in Figure 21. The samples were introduced into the spectrometer chamber without any contact with ambient atmosphere since the transfer was carried out through the N₂-filled glove-bag.

Surface Composition. The Fe/Zn and Cu/Zn atomic ratios were the simplest parameters that could be determined by XPS analysis to indicate surface stoichiometry of doped zinc oxide catalysts. For quantitative determination, the surface concentration of copper and iron in Cu/ZnO, Fe/ZnO, and Cu/Fe/ZnO catalyst was based on a model of bulk sample, i.e. particle size $\gg$ photoelectron escape depth with even distribution of dopants and taking into account an attenuation term arising from a contamination layer of carbon as described in Reference [7]. The employed first principles procedure that uses the Zn $2p_{3/2}$ line as an internal reference consisted of:

- a. deconvolution, base line correction, and integration of all peaks involved in quantification,

FIGURE 21

- b. iterative calculation of the transmission function T using Zn 2p_{1/2}, Zn 2p_{3/2}, Zn 3p, and O 1s lines along with carbon overlayer thickness by comparison of the calculated XPS intensity ratios with those experimentally observed,
- c. calculation of the photoelectron escape depth, lambda, from the Chang equation $\lambda_1 = 0.5 \sqrt{(IK)} \cdot d_i$ [8], where $d_i = 0.2824$ nm was taken to be the spacing between (10 $\bar{1}0$) planes in ZnO [9], the angular asymmetry factors were calculated using the data reported by Reilman [10], corrections of the observed XPS intensities by Scofield cross sections [11], and attenuation due to carbon overlayer [7], and
- d. calculation of the Cu/ZnO and Fe/ZnO surface ratios from the following equation:

$$\frac{X_i}{X_{Zn}} = \frac{I_i \sigma_{Zn} \lambda_{Zn} L_{Zn}(\gamma) T_{Zn} \exp(-d/\lambda_{Zn} g)}{I_{Zn} \sigma_i \lambda_i L_i(\gamma) T_i \exp(-d/\lambda_i g)}$$

where i = Cu or Fe, the angular escape factor g was taken to be 0.75 [12], X is the atomic density, and I = intensity of the XPS signal. The numerical values of all parameters used for the calculations are summarized in Table 1 and the results of the analysis are given in Table 2.

TABLE 1

XPS Parameters Used in the Surface Analysis Calculations

Element	Photoelectron Line	E.K.	sigma	lambda	L	T
Zn	2p _{3/2}	464.9	18.92	1.818	0.825	0.744
Zn	2p _{1/2}	440.7	9.80	1.186	0.825	0.742
Zn	3p	1395.0	2.83	2.111	0.810	0.823
Zn	3d	1475.5	0.81	2.17	0.878	-
O	1s	955.6	2.93	1.746	0.875	0.786
Cu	2p _{3/2}	553.8	16.73	1.329	0.825	0.751
Fe	2p _{3/2}	775.6	10.82	1.573	0.825	0.770

TABLE 2

Determination of the Surface Concentrations Of Cu and Fe Dopants in Zinc Oxide Catalysts

Catalyst	Bulk Cu/Zn Ratio	Bulk Fe/Zn Ratio	Surface Cu/Zn Ratio	Surface Fe/Zn Ratio
Cu/ZnO	0.0101	--	0.035	--
Fe/ZnO	--	0.0101	--	0.028
Cu/Fe/ZnO	0.0102	0.0112	0.036	0.035

Analyses of the surface concentrations of dopants by XPS demonstrated in all cases that the surface of the catalysts was dopant enriched. The extent of surface enrichment does not depend very strongly on the particular dopant. However, in the case of Fe/ZnO the surface enrichment was distinctly lower than those of Cu/ZnO or Fe/Cu/ZnO. The doubly doped Cu/Fe/ZnO sample showed nearly equal enrichment (3.5%) at the surface by both dopants, preserving the bulk Cu/Fe stoichiometry ratio, which is consistent with the

formation of the charge balancing $\text{Cu}^+-\text{Fe}^{3+}$ couples in the divalent ZnO matrix.

Surface Chemical State Analysis of Cu and/or Fe Doped ZnO. The typical survey XPS spectrum of a doped ZnO catalyst is shown in Figure 22, and the detailed spectra of Zn 2p, 3p, and 3d with valence band, O 1s, Cu 2p, and Fe 2p levels are presented in Figures 23-25. For all samples under investigation, the binding energy of the XPS lines listed above are reported in Table 3.

The XPS spectra are dominated by the ZnO pattern and only the most intense 2p peaks of copper and iron could be distinguished. The splitting of the 3p spectral line into Zn $3p_{1/2}$ and Zn $3p_{3/2}$ demonstrated the high resolution of the instrument. The valence

TABLE 3

Binding Energy (eV) for Cu- and/or Fe-Doped ZnO Catalysts

Catalyst	Cu 2p 3/2	Fe 2p 3/2	Zn 2p 1/2 3/2	Zn 3p 1/2 3/2	Zn 3d	O 1s
Cu/ZnO	932.8	-	1044.8 1021.7	90.9 87.9	10.4	529.8
Fe/ZnO	-	710.9	1044.7 1021.7	91.6 88.6	10.5	530.4
Cu/Fe/ZnO	933.2	711.2	1044.8 1021.7	91.4 88.5	10.4	530.3
ZnO	-	-	1044.8 1021.7	91.4 88.7	10.2	530.5

band (VB) spectra revealed the bottom valence band edge of the catalyst at 2.1 eV from the Zn 3d, while the full width at half maximum height (FWHM) was about 4.5 eV. The density of states in the VB had a maximum at 6 eV from Zn 3d (consisting mainly of 2p levels) and a second maximum at 3 eV from 3d (composed mainly of Zn 4s levels). The 3d band was located just below the valence band. An attempt was made to determine the Cu

FIGURE 22

FIGURE 23

FIGURE 24

FIGURE 25

and Fe d level position in the ZnO matrix. However, subtraction of the VB of doped ZnO from the undoped ZnO did not reveal the position of 3d Cu or Fe level due to the combined effects of their small values of scattering cross-sections and low concentrations.

Generally, the shifts of BE reflect the possible changes of the valence states, and the differences in coordinations, crystallographic sites, and spin configurations. The review of the literature core level XPS data for copper and iron (Table 4) leads to the following conclusions concerning their use for characterizing the oxidation states of Cu and Fe:

- a. Copper oxidation states Cu^+ and Cu^{2+} , as well as coordination number, can be determined from the BE of the $2p_{3/2}$ level. The Cu^{2+} usually has a well-defined satellite structure associated with the main peak with lines positioned at 3, 7.7, and 7.8 eV after the $2p_{3/2}$ line, which are assigned to ligand to metal charge transfer shake-up transitions. Cu^+ , having a completely filled d-electron shell, does not exhibit an associated satellite structure as does the paramagnetic Cu^{2+} ion. This difference helps to distinguish between Cu^+ and Cu^{2+} .
- b. Oxidation states of octahedral Fe^{2+} and Fe^{3+} are distinguishable from the BE. However, octahedral Fe^{3+} cannot be distinguished from tetrahedral Fe^{3+} , in contrast to the Fe^{2+} cation. The broad satellite structure at 729.8 eV is characteristic of an Fe^{3+} and that at 715 eV is assigned to Fe^{2+} , independent of the coordination number. Thus, combined analysis that involves position of the $2p_{3/2}$ BE line and the satellite position can be used to determine oxidation state and coordination of Fe^{2+} , but for Fe^{3+} only oxidation state can be reliably determined. The same difficulties can appear in the case of making a distinction between tetrahedral Fe^{2+} from Fe^{3+} in poorly resolved spectra, where satellite structure is smeared out due to the high noise.

TABLE 4

Binding Energies (BE), FWHM, and Satellite Structure for the 2p Regions of Cu and Fe in Different Chemical States.

Oxidation State	Co-ordination Type	2p _{3/2} BE [eV]	FWHM [eV]	Satellite structure	Ref.
Cu ⁺	O	931.3	1.5	-	11
Cu ⁺	T	932.8	1.6	-	11
Cu ²⁺	O	934.0	2.9	937 (0.55) ^a	11
Cu ²⁺	T	936.2	2.9	939.2 (0.85) ^a	11
Fe ²⁺	O	709.6	4.5	715 (w) ^b	12
Fe ²⁺	T	710.8	4.5	"	12
Fe ³⁺	O/T	711.2	4.5	719.8 (w) ^b	12

^asatellite/main peak intensity ratio

^bw = weak

The BE of the Cu 2p_{3/2} level (932.8-933.2 eV) in all catalysts under study, together with the lack of any evidence of satellite structure on the high binding energy side of the spectrum (Figure 24) indicates that this line is due Cu⁺ in tetrahedral coordination. The position of the 2p_{3/2} peak of iron at 710.9 eV for Fe/ZnO and at 711.2 eV for Cu/Fe/ZnO, along with the presence of a broad satellite at about 720 eV, agrees with trivalent iron, presumably also with tetrahedral symmetry position. However, in the case of the Fe/ZnO catalyst, the 2p_{3/2} line position may also be assigned to tetrahedral Fe²⁺.

II. CATALYTIC SYSTEMS BASED ON Cu, Fe-DOPED ZSM-5 ZEOLITE

The aim of this research was to explore (i) whether the principle of doping oxides with redox Lewis acids (cf. Fe^{III}) as well as an oxygen activating cation (cf. $\text{Cu}^{\text{I}}/\text{Cu}^{\text{II}}$) will result in oxidation of methane to formaldehyde or methanol when the oxide matrix is the ZSM-5 zeolite.

II-1. Preparation of CuFe-ZSM-5 Zeolite

Encouraging space time yields of methanol had been reported for selective methane oxidation by N_2O over CuFeZSM-5 zeolite by Anderson and Tsai [15]. A more recent report by Durante et al. [16] showed that Fe substituted sodalite also gives good conversions for the oxidation of methane to methanol by O_2 . Therefore, an aim of the present work was to verify, enhance, and modify the activity and selectivity of the CuFe ZSM-5 and sodalite catalysts. The oxidizing gas employed in this research was O_2 rather than N_2O . The two types of catalysts were synthesized via three stage procedures as outlined below.

Stage One involves the synthesis of the HFeZSM-5 or HFe sodalite materials. In both cases, the synthesis are carried out so that the Fe^{3+} ions were located in the zeolite structures in place of the usual Al^{3+} in the analogous aluminosilicate framework structures. The following synthesis methods are described in the literature [17,18] and are given here in detail.

One of the major features of the synthesis procedure is the use of low molecular weight silica species as the silica source (N-brand silica, $\text{Na}_2\text{SiO}_3 \cdot 5\text{H}_2\text{O}$; PQ Corp.) for the formation of the ferricilicate gels. By doing so, precipitation of rust-red iron hydroxide at the high pH necessary for the zeolite crystallization and complex formation of the iron with the organic template agent, which makes the FeO_2^- species unavailable for incorporation into

the zeolite framework, could be avoided. At pH values of 3-4, Fe^{3+} has the ability to precipitate low molecular weight silica species through complex formation. Once the iron is complexed in this way, the pH can be increased to basic conditions without the above undesirable effects occurring.

The synthesis procedure utilized to reach the required high pH conditions initially began with a highly acidic aqueous solution of $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ (Aldrich Chem., ACS reagent grade) that was acidified with 96% H_2SO_4 . To this solution was added an aqueous solution of the N-brand silica, and the formation of a pale yellow gel was observed. To prepare HFeZSM-5 zeolite, a template solution of tetrapropylammonium bromide (Aldrich Chem., reagent grade) was then added. To prepare HFe sodalite, a solution of tetramethylammonium chloride (Aldrich Chem., reagent grade) was added. The pH was finally adjusted to between 9 and 11 by adding 50% NaOH.

The resultant gels were heated in a Teflon-lined autoclave (Parr Instrument 125 ml high pressure bomb) at 170°C for three days under autogenic pressure. The autoclaves were mounted in a heated laboratory oven and continuously rotated on a specially constructed device at 90 rpm (see Figure 26 for the axis of rotation). In this manner, white solids were obtained that were filtered, washed, and dried at 100°C. X-Ray powder diffraction was used to confirm the synthesis of highly crystalline ferisilicate zeolites with the ZSM-5 and sodalite structures.

After removal of the template by decomposition at 550°C, a yellow (or light tan) coloring of the previously white samples seems to indicate some removal of the iron from the framework. This was observed under both N_2 and air environments. This process of template decomposition and techniques to remove the apparent extra framework Fe^{3+} species created by the decomposition procedure were investigated further.

FIGURE 26

Schematic of the Teflon-lined autoclave used for the synthesis of the Fe substituted zeolites.

In Stage Two of the synthesis procedure, the acidic forms of the zeolites were obtained by ion exchange of the zeolites with 0.1 N NH_4Cl solution. This was followed by a thermal treatment at 400°C under O_2 to remove NH_3 and retain H^+ .

Stage Three produced the Cu^{2+} exchanged forms of the Fe^{3+} substituted zeolites. This was accomplished by equilibration of the zeolites with excess 0.1 M CuSO_4 solution, followed by washing and drying under mild conditions.

This ZSM-5 zeolite prepared using this procedure contained the Fe^{3+} cations in lattice substituted sites and Cu^{2+} was present as ion exchanged cations. As mentioned, after removal of the template used during the preparation procedure by decomposition at 550°C under N_2 or air, a tan coloring of the previously white samples occurred. This seemed to indicate some removal of the iron from the framework positions. Different methods have been described in the literature to remove the apparent extra-framework Fe^{3+} species from zeolites. Until now, only the method described by Derouane et al. (19) has been used to remove these species from the zeolite ZSM-5 sample.

Derouane's procedure for removal of the extra-framework iron is as follows: the zeolite was stirred in a solution prepared by mixing a 10% NaCl solution with distilled water (with a vol ratio of 1:7) at 70°C . While stirring, $\text{Na}_2\text{S}_2\text{O}_4$ (0.25 g/g zeolite) was added, and the mixture was equilibrated for 15 min. The suspension was centrifuged and washed with distilled water to remove the residual Cl^- ions. This extraction/washing procedure was repeated five times, and then the zeolite sample was filtered and washed with distilled water.

This process primarily involves a reduction of Fe^{3+} ions to Fe^{2+} by the $\text{S}_2\text{O}_4^{2-}$ anion and thereafter ion exchange of the Fe^{2+} by Na^+ . However, this process might not be completely adequate. Upon adding the $\text{S}_2\text{O}_4^{2-}$ solution, a green coloring of the sample

occurred, indicating a reduction of the Fe^{2+} ions. However, only in the first two extractions did the washing solution become green, which showed that the extra-framework Fe^{2+} salts were removed from the zeolite. Following this, the final filtering and washing on a Buchner filter led to a reoxidation of Fe^{2+} species as concluded from the color change from the green of the wet zeolite to yellow for the filter dried sample.

The crystallinity, ZSM-5 structural framework, and purity of the ion exchanged ($\text{Cu}^{2+}, \text{NH}_4^+$)FeZSM-5 was verified by X-ray powder diffraction (XRD) at different points in the synthesis procedure, and comparisons were made with the XRD pattern obtained with a Mobil-synthesized ZSM-5 sample (see Figure 27). In the figure, pattern a was obtained with the FeZSM-5 sample immediately after synthesis, and therefore the zeolite still contained the template.

II-2. Catalyst Testing

The CuFeZSM-5 catalyst was tested using 0.1 g portions loaded into a 9 mm OD quartz reactor that narrowed into a 2 mm ID capillary immediately below the catalyst bed to allow rapid product removal. A quartz wool plug of 4-5 mm in height below the bed was used to position the catalyst in the reactor. Initially, the zeolite catalyst with particle size in the 45-75 μm range was loaded alone in the reactor. However, the pressure drop in the reactor became too high with this packed bed, and therefore the zeolite catalyst was diluted with quartz particles having dimensions in the 200-400 μm range.

Gas chromatographic product analyses were achieved by sequential on-line injection into parallel columns consisting of a 3.2 mm x 2 m Porapak Q packed fused silica column (separation of air, CH_4 , CO_2 , C_2H_4 , C_2H_6 , H_2O , and other hydrocarbons and alcohols if they form) and a 3.2 mm x 2 m packed 13X zeolite column (separation of O_2 , N_2 , CH_4 , and

FIGURE 27

CO) contained in a Hewlett-Packard 5730A GC interfaced with a 5880A integrator. Testing at each reaction temperature was typically carried out for 3.5-5.0 h, while carrying out the GC analyses at specific time intervals, such as 6-15 min. The analyses were only started after steady state stabilization of the catalyst system, which in some cases could take >3 h.

Condensable water-soluble products were collected in two water-filled scrubbers in series. The first was kept at room temperature and the second one was maintained at 0°C. Collected CH₂O was qualitatively detected by the West and Sen chromatropic acid method [1] and was quantitatively determined by the modified Romijn iodometric titration [2].

Catalytic testing was carried out at ambient pressure with a reactant mixture of CH₄/air = 1:1 with GHSV = 70,000 ℓ/kg catal/h in the temperature range of 400-850°C. The reactants consisted of ultra-high purity methane (99.97%) and zero grade air (synthetic N₂/O₂ mixture) obtained from Air Products and Chemicals, Inc. At 400°C, the conversion of reactants was detected, and the products consisted of CH₂O, CO₂, CO, and H₂O. A sharp increase in the oxygen conversion was noted at 600°C (see Figure 28), and at 850°C complete O₂ consumption was achieved. The associated temperature dependence of methane conversion, as shown in Figure 29, exhibited a parallel behavior and achieved a maximum conversion level of ≈17% at 850°C.

The principal products observed during this testing program were CO₂, CH₂O, CO, small amounts of H₂ that were not quantified, and C₂ coupling products, as well as H₂O. No methanol was detected under the reaction conditions employed.

Two main temperature regions can be distinguished with respect to the performance of the catalyst. One region occurred below 650-700°C with CH₂O as a partial oxidation product. A second region could be observed above 700°C, where mainly C₂ coupling products, together with large amounts of CO, were formed. In Figures 30-32 the selectivities

FIGURE 28

OXYGEN CONVERSION OVER CuFeZSM-5 ZEOLITE
CH₄/AIR = 1.0, GHSV = 70,000 l/kg cat/h

FIGURE 29

METHANE CONVERSION OVER CuFeZSM-5
 $\text{CH}_4/\text{AIR} = 1.0$, GHSV = 70,000 l/kg cat/h

FIGURE 30
SELECTIVITY TO FORMALDEHYDE
OVER CuFeZSM-5 ZEOLITE

FIGURE 31
SELECTIVITY TO CO₂ AND CO
OVER CuFeZSM-5 ZEOLITE

FIGURE 32
SELECTIVITY TO C₂ PRODUCTS
OVER CuFeZSM-5 ZEOLITE

FIGURE 33

CH₂O SPACE TIME YIELD
OVER CuFeZSM-5 ZEOLITE

to CH_2O , CO_2/CO , and C_2H_n ($n = 4,6$) are presented. In Figure 33, the space time yield of CH_2O is shown. It is observed that the selectivity toward CH_2O was very low over the whole temperature range. The remainder of the products at the lower temperatures were CO_2 and CO . Whether the CO was formed as a direct oxidation product of CH_4 or as a decomposition product of CH_2O has not yet been established. However, the presence of H_2 as a product at higher temperatures could favor the second pathway. In this case, the decomposition of CH_2O could be induced by slow diffusion out of the zeolite channels of the formed primary products. From Figure 31, it can be noted that the selectivity to CO remains constant (5-6%) until oxidative coupling to C_2 products is initiated (Figure 32). Thus, the behavior of CO and C_2 products selectivities tend to parallel one another.

II-3. Summary

Iron substituted ZSM-5 and sodalite zeolites have been synthesized by hydrothermal procedures. These ferrisilicate zeolites contain the Fe^{3+} cations in lattice substituted sites. Copper was subsequently added to these zeolites as ion exchanged Cu^{2+} .

CuFeZSM-5 zeolites have been prepared, partially characterized, and tested for selective oxidation of methane under the same reaction conditions as previously employed for the Cu and Fe promoted ZnO catalysts. It is found that the dual redox zeolite catalyst is very active for the oxidation of methane, and CO_2 , CO , CH_2O , and C_2 coupling products were all observed to be formed over this catalyst. The C_2 products were again observed to be formed only at the higher temperatures utilized during the testing. Formaldehyde was found to be formed over the entire temperature range, but the selectivity was uniformly low. However, because of the active nature of the catalyst, the CH_2O space time yield was as high as 113 g/kg catal/h.

III. METHANE OXIDATION OVER PALLADIUM-BASED CATALYSTS

Palladium metal is well-known to activate the C-H bond rupture in methane at significantly lower temperatures than metal oxides. The purpose of this research was to determine whether supported palladium, surface halogen-modified palladium, or palladium dispersed on catalytically active oxides will catalyze partial, rather than complete, oxidations of methane.

III-1. Preparation, characterization and testing of palladium-based catalysts

Palladium metal has been reported as a catalyst for partial oxidation of methane to formaldehyde and carbon monoxide in the presence of halogenated hydrocarbons [20,21], in contrast to the well-known behavior of Pd metal as a catalyst for the complete oxidation of methane to carbon dioxide and water in the absence of any promoters [22]. Previous work carried out in our laboratory [23] with Pd single crystals that were pretreated with dichloromethane at room temperature showed that the selectivity of the oxidation of the carbon fragments remaining from the decomposition of dichloromethane depended on the amount of this dopant preadsorbed. The higher the coverage of dichloromethane, the higher was the selectivity towards carbon monoxide relative to carbon dioxide.

Catalyst Preparation

Prior to impregnation, the SiO_2 (Davisil 636, 400 m^2/g) was equilibrated with portions of a solution of sulfuric acid (pH 3) at 100°C for two days in order to remove any Na^+ cations present on the SiO_2 . After each 2 hr equilibration, the suspension was filtered and 150 ml portions of fresh acid solution were added. The SiO_2 was then dried overnight at room temperature, dehydrated at 230°C for 4 hr, and then calcined overnight at 1000°C.

The Pd/ SiO_2 catalyst was prepared by impregnation of the SiO_2 with a solution of

palladium acetate in acetone at room temperature for 20 hr. After the equilibration, the solvent was quickly removed by heating and stirring the sample under a N₂ atmosphere. The dried product was a brown-yellow powder. The catalyst corresponded to 0.58 wt% Pd/SiO₂.

The Pd precursor/SiO₂ catalyst was heated to 180°C in air and this temperature was maintained overnight. The sample was then reduced at 160°C under a flowing gas mixture of 2% H₂/98% N₂ for 3 hr.

After this reduction treatment, the chemisorption and decomposition of CH₂Cl₂ was performed with some of the samples. The following procedure was utilized in order to ensure the removal of C and H fragments that remain after the decomposition treatment:

1. Adsorption of CH₂Cl₂ at room temperature (partial pressure of CH₂Cl₂ was < 1 mm Hg),
2. Purge the system with flowing He at room temperature,
3. Adsorption of air at room temperature,
4. Heat the sample in flowing He from room temperature to 350°C,
5. Cool to room temperature in flowing He,
6. Repeat Steps 3-5 once again,
7. Heat in flowing He from room temperature to 550°C, and
8. Cool in flowing He from 550°C to room temperature.

Characterization

The surface area of the calcined SiO₂ was 176 m²/g. The elemental analysis of the prepared catalyst was: 0.58 wt% Pd, 201 ppm Na, and 18 ppm S.

The catalyst was monitored during various stages of its preparation. For example, during the decomposition of the palladium acetate/SiO₂ precursor in air, the process was followed by differential scanning calorimetry (DSC) and gas chromatography. Two peaks were observed by DSC; one was endothermic and corresponded to the removal of the water of hydration below 100°C, and the other peak was exothermic, observed at ≈180°C, and

corresponded to the decomposition of the organic anion to CO_2 and H_2O .

During the reduction of the sample, water generation was monitored by gas chromatography. Water was detected beginning at 45°C , and traces were still observed after treating the sample at 160°C for 1 hr.

Following chemisorption of CH_2Cl_2 on the sample, the thermal decomposition of the dopant was monitored by gas chromatography but no halogenated products were detected. X-Ray photoelectron spectroscopy (XPS) analysis of the CH_2Cl_2 pretreated sample yielded strong peaks for Si, O, and C, a weak peak for Pd, and no peak for Cl.

Catalytic Testing of the Catalyst

Catalytic testing of the 0.58 wt% Pd/ SiO_2 catalyst was performed at atmospheric pressure in 6 mm Vycor microreactors. The catalyst loading consisted of 150 mg, and quartz wool plugs were used to position the catalyst bed in the reactor. Catalyst samples that were not treated with CH_2Cl_2 were tested, as well as the CH_2Cl_2 -pretreated samples so that direct comparisons could be made.

During the testing, the product analysis was carried out by gas chromatography using a HP 5890A chromatograph. On-line injection was performed into parallel columns consisting of Poraplot Q for the separation of air, CH_4 , CO_2 , C_2H_4 , C_2H_6 , and H_2O and 13X zeolite for the separation of O_2 , N_2 , CH_4 , and CO. Sampling was carried out every 15 min using a heated automated sampling valve during the 3-4 hr test at each reaction temperature.

The reactant mixture was composed of $\text{CH}_4/\text{air} = 1/1$ molar ratio and had a set gas hourly space velocity (GHSV) of 70,000 $\ell/\text{kg catal}/\text{hr}$. The air was a synthetic zero grade mixture. The catalytic tests were carried out in the temperature range of ambient

temperature to 700°C.

The methane conversion was observed to be negligible below 250°C on both the untreated and CH₂Cl₂-pretreated catalysts. Above this temperature, both of the catalysts produced only CO₂ and H₂O in similar compositions (see Figures 34-37).

These experiments suggest that the CH₂Cl₂ dopant was not adsorbed on the Pd/SiO₂ catalyst. This might be due to the surface of the catalyst being carbon-covered as a result of the decomposition of the palladium acetate precursor. If this is the case, then a better method of preparing and thermally pretreating the catalyst must be developed. However, these experiments have demonstrated that CH₄ is activated over the 0.58 wt% Pd/SiO₂ catalyst at low temperatures beginning at 300°C.

III-2. METHANE OXIDATION OVER Pd-DOPED Cu/Fe/ZnO CATALYSTS

As shown in the previous section of this report, supported Pd metal was able to activate CH₄ at low temperatures beginning at 300°C. The Pd/SiO₂ catalysts, prepared from an organic precursor of Pd acetate, were active but not selective to CH₄ partial oxidation products, since the products were CO₂ and H₂O. In order to improve the selectivity towards CH₂O, Pd was doped into Cu/Fe/ZnO catalysts that were reported in Section I-1 of this report to be good catalysts for CH₄ partial oxidation. In this way, the low temperature CH₄ activation on Pd catalysts will be combined with the CH₂O-directing ability of the Cu/Fe/ZnO catalysts.

Catalyst Preparation and Characterization

The Cu/Fe/ZnO oxide mixture was obtained according to the procedure previously reported in Section I-1. This starting mixture had a composition of 0.70 wt% Cu, 0.42 wt% Fe and 76.81 wt% Zn determined by elemental analysis, and the calcined oxide had a

FIGURE 34

0.58 w% Pd/SiO₂

GHSV=70,000 l/h kg cat CH₄/Air=1

FIGURE 35

0.58 w% Pd/SiO₂

GHSV=70,000 1/h kg cat CH₄/Air=1

FIGURE 36

0.58 w% Pd/SiO₂ CH₂Cl₂

GHSV=70,000 l/h kg cat CH₄/Air=1

FIGURE 37

0.58 w% Pd/SiO₂ CH₂Cl₂

GHSV=70,000 l/h kg cat CH₄/Air=1

surface area of 0.3 m²/g. Portions of 5 g of the Cu/Fe/ZnO mixture were impregnated with aqueous solutions of Pd nitrate (Pd(NO₃)₂ · x H₂O) of different concentrations in order to obtain a series of Pd-promoted catalysts with small doping levels of Pd.

The doping level calculations were carried out with the consideration that the oxygen anions related to the Pd cations in the PdO molecule form a close-packed monolayer on the surface of the Cu/Fe/ZnO support and the Pd cations occupy the interstices left over by the anions. Thus, the monolayer capacity for the PdO on an unit area of support can be estimated. As a result of these calculations, the monolayer capacity for PdO was 0.33 g PdO/100 m² of Cu/Fe/ZnO or 0.086 wt% Pd/Cu/Fe/ZnO.

Samples containing Pd doping levels above and below the monolayer capacity were prepared as shown in Table 5. Sample #8 was treated with distilled water to simulate the impregnation treatment.

TABLE 5

Composition of the Pd Promoted Cu/Fe/ZnO Catalysts

Sample #	Nominal Pd Composition (wt% Pd)	Elemental Composition (wt%)			
		Pd	Cu	Fe	Zn
1	1.000	0.84			
2	0.200	0.17			
3	0.100	0.0788			
4	0.020	0.0155			
5	0.010	0.0080			
6	0.002	0.0019			
7	0.001	0.0012			
8	0.000	--	0.70	0.42	76.81

The impregnating procedure was carried out at room temperature, stirring the oxide mixtures with the impregnating solutions for 12 h. Then, the samples were dried to remove

the remaining H_2O at 70-80°C for 2 days. After drying, all the samples were gray-green colored. All the samples were then calcined overnight in air at 600°C in order to make sure the decomposition of the Pd salt to PdO occurred.

Before being catalytically tested, the samples were reduced under a flowing mixture containing 2% H_2 /98% H_2 at 160°C for 3 h. XRD characterizations of the calcined samples showed the presence of ZnO and an unidentified phase, probably a Fe-Zn mixed oxide. No PdO diffraction pattern was observed in the samples.

Catalytic Testing of the Catalysts

The samples were catalytically tested at atmospheric pressure in 9 mm quartz reactors in the temperature range of ambient temperature to 750°C. The catalyst loading consisted of 114 mg, and quartz wool plugs were used to position the catalytic bed in the reactor. The reactant mixture had a $\text{CH}_4/\text{air} = 1/1$ molar ratio and the gas hourly space velocity (GHSV) was 70,000 $\ell/\text{h}/\text{kg}$ catal. The product analysis was performed by gas chromatography using a HP 5890A chromatograph. On-line injections were carried out into parallel columns consisting of a Poraplot Q capillary column for the analysis of air, CH_4 , CO_2 , C_2H_4 , C_2H_6 and H_2O and a 13 X packed column for the separation of O_2 , N_2 , CH_4 and CO. Sampling was performed every 15 min using heated automated sampling valves. The possible presence of H_2 in the gas products was not investigated. The samples were tested in steady state conditions for at least 3-4 h at each reaction temperature.

The CH_2O analysis was accomplished according to the titration technique previously described. Condensable water-soluble products were collected in two water-filled scrubbers connected in series that were kept at room temperature and 0°C, respectively. A blank test (0 wt% Pd on Cu/Fe/ZnO) was performed in order to reproduce previous results obtained

with similar catalysts but without distilled water impregnation. For the blank test (sample #8), methane conversion was observed at temperatures higher than 450°C, where the reaction products were CO₂, H₂O and CH₂O. At 700°C, the oxygen conversion was less than 10% and methane conversion was about 1%. In this temperature range, the products were always CO₂, H₂O and CH₂O, while CO or C₂ coupling products were not detected. The selectivity towards CO₂ was higher than previously observed, as described in Section I-1 of this report, probably due to the higher Cu/Fe molar ratio in the present catalyst.

For the Pd-doped samples (samples #1 to #7 in Table 5), an increase in the CH₄ conversion was obtained. Small amounts of Pd increased O₂ and CH₄ conversions at a given temperature. Methane conversions were below 4% at temperatures less than 750°C for samples with Pd compositions below monolayer capacity, as shown in Figure 38, and the corresponding CH₄ conversions were less than 40%. Methane conversions at different temperatures for Pd compositions below monolayer capacity are shown in Figure 39. The Pd doping effect seems to be a shift in the CH₄ conversion curve to lower temperatures. The higher the amount of Pd, the lower the necessary temperature to reach a given conversion. Conversions reached a maximum at 700°C at the highest Pd loadings.

Methane conversion results obtained for samples with Pd loadings above monolayer capacity are shown in Figure 40. Conversions are less than 10% at temperatures below 750°C. There is a switch in the performance of the Pd promoted catalysts at the highest loadings (1700 and 8400 ppm of Pd) since CH₄ conversion decreased when the temperature increased. This is probably due to a deactivation process in the Pd metal phase at high temperature. Figure 41 is another representation of the results, and it shows both the maximum in the CH₄ conversion curve shifted to lower temperatures as the Pd loading increased and the broad maximum obtained at the highest loading. Temperature does not

FIGURE 38

CH₄ CONVERSIONS
Cu-Fe/ZnO Pd doped CH₄/Air=1

CH₄ Conversions vs. Pd Compositions
below monolayer capacity

FIGURE 39

CH₄ Conversions vs. Temperature for Pd Compositions below monolayer capacity

FIGURE 40

CH₄ CONVERSIONS
Cu-Fe/ZnO Pd doped CH₄/Air=1

CH₄ Conversions vs. Pd Compositions
above monolayer capacity

FIGURE 41

CH₄ Conversions vs. Temperature for Pd
Compositions above monolayer capacity

seem to be an important parameter at high promoting levels, possibly indicating a different mechanism for the catalytic process.

Oxygen conversions obtained for Pd compositions below and above monolayer capacity are shown in Figures 42 and 43, respectively. The agreement between CH₄ conversions (Figures 39 and 41) and O₂ conversions (Figures 42 and 43) indicates that the main catalytic reaction was

which has a calculated CH₄/O₂ conversion ratio of 1/10 at the operating conditions previously described. This conversion ratio was obtained in almost all the experiments performed, at any temperature and at any promoter composition. Formaldehyde space time yields obtained at different temperatures for Pd compositions below monolayer capacity are shown in Figure 44. Formaldehyde yields increased as the temperature increased, and the Pd promoting effect on the CH₂O yield was more evident at high temperatures. These yields as a function of Pd composition are shown in Figure 45. At low temperatures, an increase in the Pd composition produced higher CH₂O yields, but as the temperature increased, CH₂O yield showed a maximum that shifted to lower Pd compositions. Formaldehyde yields obtained for Pd loadings above monolayer capacity are presented in Figure 46. This figure shows that the CH₂O yield curves became flatter as the Pd composition increased, in other words, Pd increased the CH₂O yield at low temperature but from 650°C, the higher the Pd loading, the lower the CH₂O yield.

Yields of CO₂ are presented in Figures 47-49, and it is evident CO₂ was the main product in all the experiments. The selectivity of CO₂ was always higher than 80%, and it reached almost 100% for the highest Pd loading at 750°C. Figure 48 shows how small Pd

FIGURE 42

O₂ CONVERSIONS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

O₂ Conversions vs. Temperature for Pd Compositions below monolayer capacity

FIGURE 43

O₂ Conversions vs. Temperature for Pd Compositions above monolayer capacity

FIGURE 44

CH₂O YIELDS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

CH₂O Space Time Yields vs. Temperature
for Pd Compositions below monolayer
capacity

FIGURE 45

CH₂O YIELDS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

CH₂O Space Time Yields vs. Pd Compositions

FIGURE 46

CH₂O YIELDS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

CH₂O Space Time Yields vs. Temperature
for Pd Compositions above monolayer
capacity

FIGURE 47

CO₂ YIELDS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

CO₂ Space Time Yields vs. Pd Compositions

FIGURE 48

CO₂ YIELDS

Cu-Fe/ZnO Pd doped

CH₄/Air=1

CO₂ Space Time Yields vs. Temperature
for Pd Compositions below monolayer
capacity

FIGURE 49

CO₂ Space Time Yields vs. Temperature
for Pd Compositions above monolayer
capacity

dopings increased CO₂ yield, compared with the sample with 0 ppm of Pd. These results confirmed that CH₄ can be activated at low temperatures by doping Pd on Cu/Fe/ZnO catalysts. Methane conversion can be improved from less than 0.04% obtained with the undoped Cu/Fe/ZnO at 550°C to 9.4% obtained with the highest Pd doped Cu/Fe/ZnO (8400 ppm of Pd) at the same temperature.

However, CH₂O selectivity was rather low and needs to be improved. The highest CH₂O space time yield obtained in this set of experiments was 57 kg/h/kg catal at 750°C with 19 ppm of Pd doped on Cu/Fe/ZnO. This value is lower than the one observed for the pure Cu/Fe/ZnO.

It is shown that Pd doped Cu/Fe/ZnO is a more active catalyst under our experimental conditions for CH₄ oxidation than the undoped one. Nevertheless, selectivity towards CH₂O is low and new operating conditions need to be set in order to improve CH₂O yield and selectivity.

III-3. FURTHER EFFECTS OF Pd LOADING IN Pd-SiO₂ CATALYSTS

As a continuation of the studies carried out with the 0.58 wt% Pd/SiO₂ catalysts, some samples of Pd-doped SiO₂ with different Pd concentrations were prepared. The purpose of the present work was to analyze the effect of operating conditions on the catalytic performance of Pd/SiO₂ catalysts as a function of the Pd loading.

Catalyst Preparation

The SiO₂ support was pretreated with sulfuric acid before impregnation with the Pd precursor according to the procedure previously described and then calcined at 670°C for 12 h. Pd/SiO₂ catalysts were prepared by impregnation of the SiO₂ support with two different Pd precursors. Preparation from organic solutions of Pd acetate have been already

described in Section III-1. The catalyst prepared by this procedure contained 0.58 wt% Pd.

A new impregnation procedure was accomplished in order to obtain C-free surfaces, since fresh calcined and reduced samples, obtained by Pd acetate impregnation, showed by XPS, C on their surfaces. The new impregnation method involved the use of the inorganic Pd nitrate precursor. Aqueous solutions of $\text{Pd}(\text{NO}_3)_2 \cdot x \text{H}_2\text{O}$, with Pd concentrations of 0.01-0.25M were used in the impregnation step. SiO_2 and the Pd nitrate solution were stirred overnight at room temperature, then samples were heated at 70°C overnight or until dryness. The resulting product was a brownish powder with Pd compositions varying between 0.66-0.88 wt%, as determined by elemental analysis.

Catalyst Activation

Calcination and reduction of the samples were performed at the operating conditions listed in Table 6.

TABLE 6

Catalyst Activation

Operating Conditions	Decomposition and Calcination		Reduction	CH_2Cl_2 Adsorption
	Pd precursor Acetate	Nitrate		
Gas	air	air	2% H_2 in N_2	in He
Temperature(C)	180	600	160	ambient
Time (h)	20	20	3	few minutes
Other				removal of C and H fragments by O_2 ads and heating

Catalyst Characterization

The surface area of the SiO_2 support after calcination at 670°C was $397 \text{ m}^2/\text{g}$, where the BET single point method was used for determination of surface areas. Catalyst surface analysis by XPS was done with a SCIENTA ESCA-300 spectrometer. Characterization by XPS was accomplished in samples prepared either from organic or aqueous solutions, and results obtained by XPS are shown in Figures 50 and 51.

When the samples were prepared from Pd acetate, C was detected on the fresh catalyst surface, indicating the presence of carbonaceous fragments remaining from the precursor decomposition (Figure 50). Well-resolved Pd $3d_{3/2}$ and $3d_{5/2}$ peaks were observed in samples with Pd loadings as low as 0.58 wt%. Cl was not detected on the surface of the CH_2Cl_2 -treated sample, indicating that the halogenated promoter had not been adsorbed on the surface of the sample because of the presence of C fragments or the amount of Cl was too small for detection by XPS.

When the samples were obtained from Pd nitrate, C was not detected on the surface. Thus, this preparation technique leads to clean, C-free fresh surfaces (Figure 51). Well-defined Pd metal peaks were observed in the reduced catalysts.

For samples prepared from Pd acetate, no PdO diffraction pattern was observed after calcination at 180°C , neither was Pd metal after reduction at 160°C .

The effect of calcination temperature on catalysts obtained from Pd nitrate (0.66 wt% Pd) is shown in Table 7. This table shows particle sizes obtained after calcination and reduction of catalysts calcined at different temperatures. No PdO diffraction pattern after calcination at 350°C was observed, but PdO particles of about $150 \text{ \AA}$ were measured at 600°C . Higher calcination temperatures lead to bigger Pd particles after reduction.

FIGURE 50

FIGURE 51

TABLE 7

Pd Particle Size by XRD Measurements After Different Thermal Treatments

Pd Loadings (wt%)	Pd Precursor	Temperature (C)		Pd Particle Size (Å)
		Calcination in air	Reduction in H ₂	
0.58	acetate	180		not detected
		180	160	not detected
0.86	acetate	180		not detected
		180	160	not detected
0.66	nitrate	350		not detected
		350	160	100
		600		150
		600	160	220
0.88	nitrate	600		180
		600	160	85
		600	160	130*

* after catalytic test at 600°C

Catalytic Testing

Samples were tested at atmospheric pressure and at different temperatures in quartz reactors. The diameter of reactors used in the catalytic tests varied from 9 to 13 mm. During these tests, new calibrations were made in order to quantify H₂. Argon was used as carrier gas for this purpose, and the response factors of all the compounds have been determined.

The catalyst loading consisted of 114 mg and the reactant mixture was either CH₄ + air or CH₄ + O₂ + N₂ with different CH₄/O₂ ratios. The CH₄/air ratio varied between 1-4 and the gas hourly space velocity (GHSV) between 70,000-130,000 l/h/kg catal.

Catalysts prepared either from aqueous or organic impregnation produced mainly

CO₂. Catalytic activity was observed at temperatures as low as 300°C.

Treatment with Halogenated Promoter. In some cases, CH₂Cl₂ adsorption was performed on fresh and used catalysts. Figure 52 shows the results obtained after different treatments with a 0.58 wt% Pd/SiO₂ catalyst. Cl-free and CH₂Cl₂-treated used catalyst samples showed similar catalytic behavior and only CO₂ was obtained at low temperature. However, CH₂Cl₂ adsorption performed on a fresh Pd metal surface showed an enhanced activating effect in terms of CH₄ conversion at a lower temperature. Subsequently to this testing, no evidence that adsorption of the halogenated promoter had taken place was observed by chemical and surface analysis.

Effect of Pd doping. Results obtained with catalysts containing different Pd concentrations are shown in Figures 53-57. It was observed that methane conversion decreased with Pd doping at high temperatures (Figures 53 and 54). At low temperatures, below 350°C, the effect seems to be the opposite, and the higher the Pd doping, the higher the methane conversion.

Formaldehyde was obtained at very low concentrations with all the catalysts. In addition, CO + H₂ were detected at temperatures higher than 400°C. The formaldehyde concentration decreased at temperatures above 400°C, indicating that the CO and H₂ production was a consequence of CH₂O decomposition. This effect was observed for all the samples regardless their composition (Figures 55-57). Selectivity to CO increased with temperature and decreases with Pd loading (Figure 54).

Effect of CH₄/O₂ Ratio. This effect of reactant ratio has been studied at three different reaction conditions, as shown in Figures 58 and 59. At the reaction temperature

FIGURE 52

Pd/SiO₂ (0.58% Pd) different treatments

GHSV=70,000 l/h kg

CH₄/Air=1

FIGURE 53

Pd/SiO₂ different Pd compositions
GHSV=70,000 l/h kg CH₄/Air=1

FIGURE 54

Pd/SiO₂ different Pd compositions
GHSV=70,000 l/h kg CH₄/Air=1

FIGURE 55

Pd/SiO₂ (0.58 % Pd) sample: 1Pd10
GHSV=70,000 l/h kg CH₄/Air=1

FIGURE 56

Pd/SiO₂ (0.66 % Pd) sample: N2Pd67
 GHSV= 70,000 l/h kg CH₄/AIR=1

—■— CO₂

—□— H₂O

—▲— CH₂O x 1000

—□— CO

FIGURE 57

Pd/SiO₂ (0.88 % Pd) sample: N1 Pd67
 GHSV= 70,000 l/h kg CH₄/AIR=1

—■— CO₂ —□— H₂O —*— H₂
 —□— CO —▲— CH₂O x 1000

FIGURE 58

Pd/SiO₂ (0.88 % Pd) sample: N1 Pd67
TEMPERATURE= 500 C

FIGURE 59

Pd/SiO₂ (0.88 % Pd) sample: N1Pd67
TEMPERATURE= 500 C

of 500°C, CH₄ conversions below 5% were obtained with GHSV = 130,000 l/h/kg catal. The selectivity to H₂ and CH₂O increase with the CH₄/O₂ ratio (Figure 59). However, selectivity to CO decreases upon an increase in CH₄/O₂ ratio. This seems to indicate that CO and H₂ do not come from the same source.

Conclusions. Big Pd metal particles of about 200 Å are obtained after the thermal treatments using the preparation procedures employed in this work. The surfaces of catalysts prepared from Pd acetate were not C-free. It was shown that CH₄ can be activated on Pd catalysts at temperatures as low as 300°C. CH₂Cl₂ adsorption and decomposition apparently did not take place on the C-covered Pd surfaces. Some promoting effect was observed when the CH₂Cl₂ adsorption was carried out on fresh, clean surfaces, but no Cl was detected on the surface after testing.

In all cases, CO₂ was the main product, regardless of Pd composition or operating conditions. Pd did promote CH₄ activation, but at high Pd loadings there was a sintering process that led to lower activities. Formaldehyde was obtained in small amounts over the Pd catalysts but it decomposes at higher temperatures to give CO and H₂.

III-4. Summary

Catalytic properties of Pd/SiO₂ catalysts prepared by impregnation from different Pd precursors, have been investigated. Catalytic tests were carried out under a flowing mixture of CH₄, N₂ and O₂ with different CH₄/O₂ ratios and GHSV. Some of the samples were pretreated with CH₂Cl₂ as halogenated promoter. Experimental evidence was obtained that CH₂Cl₂ modifier did not chemisorb and dissociate on Pd/SiO₂ catalysts that were apparently surface contaminated with carbon. However, it was demonstrated that a 0.58 wt% Pd/SiO₂ catalyst exhibited high activity in the low temperature range of 325-340°C for the complete

oxidation of CH₄.

In order to combine the low temperature activity of the Pd catalysts with the partial oxidation selectivity of the Cu/Fe/ZnO catalysts, a series of Pd-doped Cu/Fe/ZnO catalysts have been prepared, and methane oxidation over the palladium-doped dual redox catalysts has been accomplished. The Pd promoting effect on the activity and selectivity of Cu/Fe/ZnO oxide mixtures has been studied in order to compare the resultant catalytic activity with the performance of the undoped Cu/Fe/ZnO catalyst under similar experimental conditions. Pd supported on Cu/Fe/ZnO showed a higher catalytic activity than the undoped ternary oxide mixture in the methane oxidation reaction at low temperatures. However, the selectivity to formaldehyde formation of the Pd doped catalyst was lower than that observed with the undoped catalyst.

The main reaction products obtained with the Pd doped catalysts were carbon dioxide and water under the reaction conditions that were employed, indicating that complete methane oxidation was promoted by the Pd promoter.

IV. OXIDATIVE COUPLING OF METHANE OVER Fe, Sn, Bi AND Sb-DOPED STRONTIUM-LANTHANA CATALYSTS

The purpose of investigating the modified SrO/La₂O₃ catalysts for partial oxidation of methane was (i) to lower the reaction temperatures for methane coupling to C₂ products to a commercially acceptable range, 600°C and below, and (ii) to determine whether the selectivity pattern has been influenced by the dopants. Because the SrO/La₂O₃ catalysts are very basic, the dopants chosen were acidic oxides, and the elements therein were also potential redox systems, viz. Fe^{II}/Fe^{III}, Sn^{II}/Sn^{IV}, Bi^{III}/Bi^V, and Sb^{III}/Sb^V.

IV-1. Preparation, Characterization, and Testing of the FeO_x/SrO/La₂O₃ Catalyst

Lanthanide-based oxides are well-known catalysts for oxidative coupling of methane toward C₂ products [24-26]. However, the temperatures for their use are still too high (750-850°C) for the process to be commercially attractive. In this investigation, the role of Fe^{III} dopants on the methane oxidation and C₂ selectively over SrO/La₂O₃ has been explored. As a first step, the activity and selectivity of methane oxidation coupling to C₂ hydrocarbons over the base SrO/La₂O₃ catalyst was reproduced. The catalyst was received from AMOCO Oil Co. where it was prepared in a large batch for distribution under their Universities Natural Gas Conversion Program. The data obtained with the SrO/La₂O₃ catalyst were found to be reproducible and the catalyst displayed the reported high activity and selectivity to C₂ hydrocarbons at 750°C with an ethylene-to-ethane ratio equal to 0.87.

Preparation of Fe³⁺ Doped Sr/La₂O₃ Catalyst

A 1 wt% Sr/La₂O₃ catalyst was obtained from AMOCO Oil Co., which was synthesized as described in References 25 and 26. The catalyst was a white, hygroscopic powder. A nominally 1 wt% Fe/1 wt% Sr/La₂O₃ catalyst was prepared by aqueous

impregnation of the original $\text{Sr/La}_2\text{O}_3$ sample with $\text{Fe}(\text{NO}_3)_3 \cdot 9 \text{H}_2\text{O}$, using a solution volume equivalent to three times the pore volume as provided by AMOCO Oil Co. The sample was stirred overnight at ambient temperature and then the remaining solvent was evaporated to dryness under stirring. Final drying was carried out in an Ar flow at 80°C for 66 h. The impregnated catalyst was then decomposed in Ar at 140°C for 3 h, followed by calcination in Ar at 600°C for 21 h. The sample was pale-yellow after drying and decomposition and became gray after calcination.

Catalyst Characterization

Characterization by X-ray powder diffraction (XRD) was performed after different thermal treatments. Figure 60 shows the diffraction pattern obtained for the $\text{Sr/La}_2\text{O}_3$ sample as received. There are three phases identifiable in the diffractogram: La_2O_3 (hexagonal), ASTM 5-602; La_2O_3 (cubic), ASTM 22-369; $\text{La}(\text{OH})_3$, ATM 36-1481. The most intense peaks belong to the hexagonal La_2O_3 . The presence of $\text{La}(\text{OH})_3$ is probably due to the fact that the lanthanum oxides are hygroscopic. The remaining phase, the cubic La_2O_3 , showed less intense peaks, indicating that this phase is a minor component of the solid.

Figure 61 shows the diffraction pattern of $\text{Sr/La}_2\text{O}_3$ after further activation in Ar at 700°C . Only one phase was detected, the hexagonal La_2O_3 . The intensity of the pattern was higher than that of the untreated sample, indicating an increase in crystallinity. In Figure 62, the diffraction pattern obtained after the $\text{Sr/La}_2\text{O}_3$ was catalytically tested at 850°C is shown. Only the hexagonal La_2O_3 was detected, and the main difference compared to Figure 61 is the presence of doublets at $2\theta > 60^\circ$.

Sample: C File: ID21.SM

Sample: A File: ID19.SM

FIGURE 61

XRD pattern of Ar-activated Sr/La₂O₃ catalyst at 700 C

Sample: B File: ID20.SM

The Fe/Sr/La₂O₃ sample was almost X-ray amorphous after Ar calcination at 600°C, as shown in Figure 63. The only phase detected was La(OH)₃ with peak intensities that were similar to those observed in Figure 60 for the Sr/La₂O₃ catalyst without thermal treatment. It seems that the preparation procedure involving aqueous impregnation hydrolyses the oxide and causes the disappearance of the hexagonal La₂O₃ phase [27]. Even though some researchers [28] report that the La(OH)₃ can be reconverted to the original La₂O₃ by heating at 450-500°C, this was found not to occur even at higher temperatures (600°C). In an attempt to reconvert the hydroxide into La₂O₃, the Fe/Sr/La₂O₃ catalysts calcined in Ar at 600°C was subsequently fired at 1000°C. The diffraction pattern obtained after this treatment is shown in Figure 64, and this diffraction pattern shows well-crystallized phases of La(OH)₃ and La₂O₃, but the La(OH)₃ is still the major component. No La-Sr, La-Fe, or Fe-Sr phase was evident by XRD.

Catalytic Tests

The catalytic testing was performed using a CH₄ and air mixture with CH₄/Air = 1. The GHSV was 70,000 ℓ/kg cat/h, and the catalyst load was 0.114 g. Samples were loaded in 9 or 13 mm diameter (OD) quartz reactors. A set of experiments was carried out in the temperature range of 500-850°C and at atmospheric pressure.

Sr/La₂O₃. Results obtained with the Sr/La₂O₃ catalyst are shown in Figures 65-70. Methane conversions were about 23% at temperatures higher than 650°C. The space time yields (STY) of C₂ products (ethylene & ethane) were about 3000 g C₂/kg cat/h at temperatures higher than 700°C (Figure 66). Figure 67 shows the yield % of products as the sum of C₁ (CO+CO₂), C₂, and C₃ products. At temperatures higher than 650°C, the highest yield corresponded to the C₂ products.

Sample: D File: ID22.SM

FIGURE 63

XRD pattern of Fe/Sr/La₂O₃ catalyst calcined
in Ar at 700 C

Sample: Fe/Sr/La2O3 1000 C File: ID23J04.SM

FIGURE 65

1 wt% Sr/La₂O₃ CONVERSIONS

GHSV = 70,000 l/h kg

CH₄/AIR = 1

FIGURE 66

1 wt% Sr/La₂O₃ S.T.Y.
GHSV = 70,000 l/h kg CH₄/AIR=1

FIGURE 67

1 wt% Sr/La₂O₃
GHSV = 70,000 l/h kg

YIELDS (%)
CH₄/AIR = 1

FIGURE 68
1 wt% Sr/La₂O₃ SELECTIVITIES
GHSV = 70,000 l/h kg CH₄/AIR=1

FIGURE 69

1 wt% Sr/La₂O₃ SELECTIVITIES

GHSV = 70,000 l/h kg

CH₄/AIR = 1

—■— SUM C1 —□— SUM C2 —□— SUM C3

FIGURE 70

The catalyst had a good selectivity toward C_2 products as shown in Figures 68 and 69. At low temperatures, the main products are CO_2 and CO , but selectivity toward C_2 products increased with increasing temperature. The production of C_3 compounds was observed at 700-750°C. Figure 70 shows the $C_2= / C_2$ and CO / CO_2 ratio. The molar ratio for the C_2 products increases with increasing temperature, and the C_1 products ratio is about constant at high temperatures. Negligible amounts of CH_2O were obtained with this catalyst.

Fe/Sr/La₂O₃. The results obtained with the Fe-doped Sr/La₂O₃ are shown in Figures 71-76. The Fe promoted catalyst was more active at lower temperatures, but methane conversions were about 20% at temperatures higher than 700°C. Oxygen conversions at those temperatures were about 25%. Figure 72 shows results in terms of space time yields (STY). The comparison between the Fe/Sr/La₂O₃ and Sr/La₂O₃ catalysts indicates that the CO_2 STY is higher on the Fe/Sr/La₂O₃, while the STY of CO is lower. The STY of C_2 products was lower than that obtained with the Sr/La₂O₃ catalyst.

Figure 73 shows yields (%) as C_1 , C_2 , and C_3 products. Comparison between Figures 67 and 73 shows that C_2 and C_3 product yields were higher on the Sr/La₂O₃ catalyst. The performance of the Fe/Sr/La₂O₃ catalyst in terms of selectivities is similar to that of Sr/La₂O₃ catalyst, with selectivities toward CO and CO_2 being the main difference between the catalysts (Figures 68 and 74). Figure 75 shows the product selectivities calculated as C_1 , C_2 , and C_3 products. Selectivity toward C_2 products was about 50% at temperatures higher than 750°C.

In Figure 76, the $C_2= / C_2$ and CO / CO_2 ratio are shown. Similar behavior was obtained with the Fe/Sr/La₂O₃ catalysts in terms of the $C_2= / C_2$ ratio increasing with increasing temperature compared with the Sr/La₂O₃ catalyst. A straight line was observed

FIGURE 71

1wt% Fe/1wt% Sr/La₂O₃
GHSV = 70,000 l/h kg

CONVERSIONS
CH₄/AIR=1

FIGURE 72
1wt% Fe/1wt% Sr/La₂O₃ S.T.Y.
GHSV = 70000 l/h kg CH₄/AIR=1

FIGURE 73

1wt% Fe/1wt% Sr/La₂O₃ YIELDS (%)
GHSV = 70000 l/h kg CH₄/AIR = 1

FIGURE 74
1wt% Fe/1wt% Sr/La₂O₃ SELECTIVITIES
CH₄/AIR=1
GHSV= 70,000 l/h kg

FIGURE 75

1wt% Fe/1wt% Sr/La₂O₃

GHSV = 70,000 l/h kg

SELECTIVITIES

CH₄/AIR = 1

—■— SUM C1 —□— SUM C2 —⊠— SUM C3

FIGURE 76

1wt% Fe/1wt% Sr/La₂O₃ PRODUCTS RATIO
GHSV= 70,000 l/h kg CH₄/AIR=1

for the $C_2=$ / C_2 ratio, but the slope was smaller than that observed with the Sr/La₂O₃ catalyst. The CO/CO₂ ratio was almost constant and lower than that for Sr/La₂O₃, indicating that the production of CO is not favored on the Fe/Sr/La₂O₃ catalyst. Formaldehyde was detected over the Fe/Sr/La₂O₃ catalyst in even lower concentrations than those quantified for the Sr/La₂O₃.

Conclusions

Apparently, the Fe-doping of Sr/La₂O₃ catalyst carried out under the present conditions, does not enhance the performance of that catalyst in terms of selectivity toward oxygenates. Upon doping the Sr/La₂O₃ catalyst with Fe, the respective concentrations of CO and CH₂O were lower than those obtained with the undoped catalyst.

IV-2. Preparation, Characterization and Testing of the SbO_x/SrO/La₂O₃, BiO_x/SrO/La₂O₃ and SnO_x/SrO/La₂O₃ Catalysts

Preparation and Characterization

The base catalyst again consisting of 1 wt% Sr/La₂O₃, prepared as described by DeBoy and Hicks [26], was obtained from AMOCO Oil Co. The acidic promoters consisting of Sb³⁺, Sn²⁺, and Bi³⁺ were doped by aqueous impregnation onto the base catalyst using the SbCl₃, Sn(CH₃COO)₂, and Bi(NO₃)₃•5H₂O salts, respectively. After drying under stirring for 30 h at 100°C, samples were calcined at 600°C for 20 h. The doped oxides had a final composition of ≈0.5/1.0/88.5 wt% M/Sr/La₂O₃ as determined by elemental analysis, where M = Sb, Sn, or Bi. The surface areas of both the unpromoted and the promoted Sr/La₂O₃ catalysts are shown in Table 8.

Surface doping was confirmed by X-ray photoelectron spectroscopy (XPS), which showed that the dopants were dispersed on the surface of the Sr/La₂O₃ catalyst to 18%,

34%, and 37% of the monolayer coverage for SnO_2 , Bi_2O_3 and Sb_2O_3 , respectively. The surface atomic ratios determined from the XPS spectra obtained with the SCIENTA ESCA-300 high resolution instrumental at Lehigh University are presented in Table 8.

Table 8. Surface Areas and Surface Atomic Ratios of the Unpromoted and Promoted $\text{Sr/La}_2\text{O}_3$ Catalysts.

Catalyst	Surface Areas (m^2/g)	Surface Atomic Ratios					
		$X_{\text{Sr}}/X_{\text{La}}$	$X_{\text{Sn}}/X_{\text{La}}$	$X_{\text{Bi}}/X_{\text{La}}$	$X_{\text{Sb}}/X_{\text{La}}$	$X_{\text{O}}/X_{\text{La}}$	$X_{\text{C}}/X_{\text{La}}$
$\text{Sr/La}_2\text{O}_3$	6.5	1.37	-	-	-	4.1	1.03
$\text{Sn/Sr/La}_2\text{O}_3$	16.3	1.21	0.14	-	-	2.9	0.55
$\text{Bi/Sr/La}_2\text{O}_3$	17.4	1.10	-	0.16	-	2.8	0.90
$\text{Sb/Sr/La}_2\text{O}_3$	17.2	1.16	-	-	0.23	2.9	0.51

Catalytic Testing

The catalytic testing was performed in a 9 mm OD quartz fixed-bed continuous-flow microreactor at ambient pressure in the temperature range of 450-850°C. The load of the catalyst was 0.114 g. A reactant mixture of CH_4 and air with a $\text{CH}_4/\text{air} = 1$ molar ratio GHSV of 70,000 $\ell/\text{h kg cat}$ (STP) was used. The exiting gases consisting of $\text{C}_2 =$ (ethene), C_2 (ethane), $\text{C}_3 =$ (propene), C_3 (propane), CH_4 , CO , CO_2 , H_2O , N_2 and O_2 were analyzed by on-line gas chromatography using a TC detector and Poraplot QS capillary and 13X zeolite columns. Samples were activated under He flow at 700°C for 3 h before the catalytic testing in order to remove traces of water and to make sure the lanthana was present as La_2O_3 (ASTM 5-602).

The promoted $\text{Sr/La}_2\text{O}_3$ catalysts showed measurable activity at a reaction temperature of 500°C, especially the $\text{Sn/Sr/La}_2\text{O}_3$ catalyst that exhibited 14.0% methane

conversion at that temperature. For comparison of the unpromoted Sr/La₂O₃ and the promoted M/Sr/La₂O₃ catalysts, steady state results for the catalytic tests at 600°C are summarized in Table 9. The performance of the doped Sr/La₂O₃ catalysts has been clearly improved by the acidic promoters in terms of both yield toward C₂ products and the C₂=/C₂ ratio, with the Sb/Sr/La₂O₃ catalyst being the most active and selective under those conditions. The C₂ promoting effect is also evident in the suppression of CO_x products, which dropped from a CO_x selectivity of 69.3% for the unpromoted Sr/La₂O₃ to 39% for the Sb/Sr/La₂O₃ catalyst. The effect of the acidic components was also evident by lowering significantly the temperature of the reaction, as shown in Figure 77. The doped catalysts achieved high yields toward C₂ products at lower temperatures (500-600°C) than that obtained with the unpromoted Sr/La₂O₃ (650-800°C). At the higher temperatures, all catalysts reached the same methane conversion because of the depletion of the oxygen reactant, and as a consequence, they showed about the same yield toward C₂ products. The

Table 9. Activity and Selectivity of Strontia-Lanthana Based Catalysts for Oxidative Coupling of Methane.^a

Catalyst	CH ₄ Conv. ^b	Selectivities ^c					Total C ₂ +C ₂ = Yield ^d	C ₂ =/C ₂
		C ₂ =	C ₂	C ₃ +C ₃ =	CO	CO ₂		
Sr/La ₂ O ₃	8.8	5.3	25.3	-	23.9	45.4	2.7	0.21
Sn/Sr/La ₂ O ₃	18.8	18.9	28.9	3.7	6.7	41.8	9.0	0.65
Bi/Sr/La ₂ O ₃	22.2	23.5	31.1	4.6	3.7	37.1	12.1	0.76
Sb/Sr/La ₂ O ₃	23.5	25.2	32.3	3.4	5.0	34.0	13.5	0.78

^aReaction conditions: T = 600°C, GHSV = 70,000 l/h kg cat, CH₄/air = 1.

^bmol %. ^ccarbon atom %. ^dDefined as methane conv. x selectivity %.

FIGURE 77

Effect of temperature on the yield of total C_2 products for the unpromoted and acid-promoted Sr/La_2O_3 catalysts with $CH_4/air = 1$ at $GHVS = 70,000 \text{ l/h kg cat}$ and 0.1 MPa .

Sn-doped catalyst was found to have higher stability than the Sb- or Bi-doped catalysts since these oxides tended to volatilize at temperatures above 700°C. However, stability tests performed at 600°C showed that all of the acidic-doped catalysts were stable and did not deactivate over 100 h runs, and an example is shown in Figure 78 for the Sb/Sr/La₂O₃ catalyst.

The results obtained with the acid-promoted Sr/La₂O₃ catalysts correlate with the acidic properties of the dopants, so that the higher the electronegativity [29] of the dopant cations, the higher the methane conversion and the selectivity toward C₂ products. This suggests that the role of the Sb, Sn and Bi oxides is to increase the residence time of the •CH₃ radicals generated by the Sr/La₂O₃ catalyst near the surface by equilibria between the gaseous methyl radical and its carbenium ion bound to the acid oxide component. Further, the strong interaction expected between the strongly basic oxide matrix of Sr/La₂O₃ and the acidic dopants is proposed to stabilize the Sr/La₂O₃ catalyst in its oxide state by preventing carbonate and hydroxide formation. Thus, the promotional effect of the Sb, Bi, and Sn dopants shifts both the activity and selectivity for the oxidative coupling of methane toward lower temperatures, as shown in Figure 77. Further studies need to be carried out to fully understand the promoting mechanism.

Summary

It has been found that surface doping of the SrO/La₂O₃ oxide catalyst by small amounts of acidic oxides (≈0.5 wt%) of the lower right side of the periodic table, specifically Group IVA and VA metal oxides such as Sb, Bi, and Sn, greatly enhances the activity toward C₂ coupling products and lowers the temperature of ethene and ethane production by about 150°C. At the same time, the olefin/paraffin ratio (C₂=/C₂ = ethene/ethane) is

significantly increased by the dopants at any given temperature. The resultant space time yields are very high, e.g. 100 mol of total C₂ product/h kg cat with the Sb/Sr/La₂O₃ catalyst at 600°C.

We appreciate receiving the undoped Sr/La₂O₃ catalyst from AMOCO Oil Co. under the AMOCO University Methane Conversion Program.

FIGURE 78

Sb STABILITY TEST

600°C GHSV = 70000 l/h kg CH₄/air = 1

■ CO₂ □ C₂= ▲ C₂
 ⊠ C₃ ⊗ CO

REFERENCES

1. P. W. West and B. Sen, Z. Anal. Chem., 153, 177 (1956).
2. G. Romijn, Z. Anal. Chem., 36, 19 (1877).
3. A. I. Vogel, "Quantitative Inorganic Analysis," Wiley Publ., 287 (1961).
4. R. G. Herman, K. Klier, G. W. Simmons, B. P. Finn, J. B. Bulko, and T. P. Kobylinski, J. Catal., 56, 407 (1979).
5. C. Greskovich and K. W. Lay, J. Am. Ceram. Soc., 55, 142 (1972).
6. K. Hirokawa and M. Oku, Talanta, 26, 855 (1979).
7. M. J. Dreiling, Surface Sci., 71, 231 (1978).
8. C. C. Chang, Surface Sci., 48, 9 (1975).
9. G. A. Vedage, P. B. Himelfarb, G. W. Simmons, and K. Klier, ACS Symp. Ser., 279, 295 (1985).
10. R. F. Reilman, A. Msezane, and S. T. Manson, J. Electron. Spectrosc., 8, 389 (1976).
11. J. H. Scofield, J. Electron. Spectrosc., 8, 129 (1976).
12. M. P. Seah, Surface Sci., 32, 703 (1972).
13. A. d'Uysser, B. Ierebours-Hannoye, M. Lenglet, and J. P. Bonnelle, J. Solid State Chem., 39, 246 (1981).
14. C. R. Brundle, T. J. Chuang, and K. Wandelt, Surface Sci., 68, 459 (1977).
15. J. R. Anderson and P. Tsai, J. Chem. Soc., Chem. Commun., 1435 (1987).
16. V. A. Durante, D. W. Walker, W. H. Seitzer, and J. E. Lyons, Preprints, Symp. on Methane Activation, Conversion, and Utilization, Intern. Chem. Congr. Pacific Basin Societies, 23 (1989).
17. R. Szostak and T. L. Thomas, J. Chem. Soc., Chem. Commun., 113 (1986).
18. R. Szostak, V. Nair, and T. L. Thomas, J. Chem. Soc., Faraday Trans. 1, 83, 487 (1987).
19. E. G. Derouane, M. Mestdagh, and L. Vielvoye, J. Catal., 33, 169 (1974).
20. C. F. Cullis, D. E. Keene, and D. L. Trimm, J. Catal., 19, 378 (1970).

21. R. S. Mann and M. K. Dosi, J. Chem. Technol. Biotechnol., **29**, 467 (1979).
22. R. B. Anderson, K. C. Stein, J. J. Freeman, and L. J. Hofer, Ind. Eng. Chem., **53**, 809 (1961).
23. Y.-N. Wang, J. A. Marcos, G. W. Simmons, and K. Klier, J. Phys. Chem., **94**, 7597 (1990).
24. C.-H. Lin, K. D. Campbell, J. X. Wang, and J. H. Lunsford, J. Phys. Chem., **90**, 534 (1986).
25. J. M. DeBoy and R. F. Hicks, Ind. Eng. Chem. Res., **27**, 1577 (1988).
26. J. M. DeBoy and R. F. Hicks, J. Catal., **113**, 517 (1988).
27. M. P. Rosynek and D. T. Magnuson, J. Catal., **46**, 402 (1977).
28. C. Sudhakar and M. A. Vannice, Appl. Catal., **14**, 47 (1985).
29. K. Tanaka and A. Ozaki, J. Catal., **8**, 1 (1967).

END

**DATE
FILMED**

2 / 2 / 93