DOE/PC/91345 -- T8

1-3
(3)

**A NOVEL CARBON-BASED PROCESS
FOR FLUE GAS CLEANUP**

**Seventh Quarterly Technical Progress Report
January 1 to March 31, 1993**

**Contract No. DE-AC²21-91PC91345
Ms. Diane Revay Madden: DOE COR**

Submitted to:

**U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940, Pittsburgh, PA 15236**

**S.K. Gangwal, Project Manager
Research Triangle Institute
Research Triangle Park, NC 27709
(919) 541-8033**

**P.L. Silveston, Co-Principal Investigator
University of Waterloo
Waterloo, Ontario, Canada N2L3G1
(519) 885-1211, Ext. 2534**

April 1993

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

yr BD
no Inv

RECEIVED
JUN 14 1993
OSTI

**A NOVEL CARBON-BASED PROCESS
FOR FLUE GAS CLEANUP**

**Seventh Quarterly Technical Progress Report
January 1 to March 31, 1993**

**Contract No. DE-AC21-91PC91345
Ms. Diane Revay Madden: DOE COR**

Submitted to:

**U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940, Pittsburgh, PA 15236**

**S.K. Gangwal, Project Manager
Research Triangle Institute
Research Triangle Park, NC 27709
(919) 541-8033**

**P.L. Silveston, Co-Principal Investigator
University of Waterloo
Waterloo, Ontario, Canada N2L3G1
(519) 885-1211, Ext. 2534**

April 1993

TABLE OF CONTENTS

<u>Section</u>		<u>Page</u>
	List of Tables and Figures	ii
	Abstract	iii
1.0	INTRODUCTION	1
	1.1 Objective	1
	1.2 Process Description	1
	1.3 Background	2
	1.4 Project Scope/Schedule	4
	1.5 Measures of Success	6
2.0	WORK COMPLETED IN PREVIOUS QUARTERS	6
3.0	WORK COMPLETED IN PRESENT QUARTER	7
	3.1 Accomplishments	7
	3.2 SO ₂ Removal	7
	3.2.1 SO ₂ Removal Experiments at 21°C	7
	3.2.2 SO ₂ Removal Experiments at Higher Temperatures	7
	3.3 NO _x Removal	8
4.0	WORK PLANNED FOR NEXT QUARTER	8
	4.1 SO ₂ Removal	8
	4.2 NO _x Removal	8
	4.3 Process Evaluation	8
5.0	REFERENCES	10
6.0	APPENDIX I	11
	APPENDIX II	25

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LIST OF TABLES

Table 1	Advantages of Process	2
Table 2	Catalysts Tested for NO Removal	8
Table 3	NO_x Conversion Test Results	9

LIST OF FIGURES

Figure 1	Flue gas cleanup process concept	1
Figure 2	Multistage activated carbon scrubbing process with pulsed liquid flow and cooling of the feed gas and reheating of the off-gas by heat recovery	3

ABSTRACT

The objective of this project is to demonstrate the preliminary technical and economic feasibility of a novel carbon-based process for removal of at least 95% SO_2 and at least 75% NO_x from coal combustion flue gas. In the process, flue gas leaving the electrostatic precipitator (ESP) is passed through a trickle bed of activated carbon catalyst employing a periodic flush of low strength sulfuric acid. The SO_2 is oxidized to SO_3 and removed as medium strength sulfuric acid. The SO_2 -free flue gas is then mixed with NH_3 , and the NO_x in the gas is subjected to selective catalytic reduction (SCR) to N_2 over a fixed bed of activated carbon catalyst.

The project is being carried out over 23 months (June 4, 1991, to April 30, 1993). The experimental work is divided between Research Triangle Institute (RTI) and the University of Waterloo (Waterloo). RTI will primarily conduct the NO_x removal studies, whereas Waterloo will conduct most of the SO_2 removal studies. The ultimate goal of the project is to demonstrate that the process can reduce the cost of electricity by 20% over conventional SCR/flue gas desulfurization (FGD) processes.

In the previous six quarters, detailed project plans were prepared and experimental systems were commissioned. The SO_2 removal factorial experiments with BPL carbon at 21°C are well underway at Waterloo. A modified carbon catalyst (MCCI) showed up to 99% SO_2 removal in the presence of NO_x over 10 multiple cycles at $80\text{--}130^\circ\text{C}$ and 1400 scc/cc/h. Several catalysts were evaluated for NO_x removal also. Promising modified carbon catalysts (MCCI, II and III) were tested. Some of these catalysts showed the potential for over 80% NO_x removal at space velocities as high as 3000 scc/cc/h. Poisoning of NO_x removal efficiency with SO_2 in the feed was also studied. With over 100 ppm SO_2 in feed, NO_x removal efficiency remained steady for several hours. It declined from 79% removal to 66% removal over 24 hours. Papers were presented at the Minneapolis AIChE Meeting and the Contractor's Meeting and a detailed economic evaluation report was prepared. Papers were prepared for the U.S. Japan workshop and the Third Sheffield International Symposium. In the present quarter, NO_x removal experiments were performed with 5 different materials and the SO_2 removal activity of 2 catalysts was tested.

1.0 INTRODUCTION

1.1 OBJECTIVE

The objective of this project is to demonstrate the preliminary technical and economic feasibility of a novel carbon-based process for removal of at least 95% SO_2 and at least 75% NO_x from coal combustion flue gas. The process is based on the demonstrated ability of activated carbons to catalyze SO_2 oxidation and NO_x reduction below 150°C .

1.2 PROCESS DESCRIPTION

The process concept is shown in Figure 1. The hot flue gas leaves the electrostatic precipitator (ESP) at $\sim 150^\circ\text{C}$ and enters a recuperative gas-gas heat exchanger, employing a bed of ceramic balls, to cool the flue gas for SO_2 removal and simultaneously heat the cold flue gas for NO_x removal. The gas leaving the exchanger enters a series of two to three activated carbon trickle-bed catalytic reactors at approximately 100°C to remove the SO_2 and convert it to medium strength sulfuric acid. The essentially SO_2 -free gas from the last trickle bed goes through the exchanger to the NO_x converter. The required amount of NH_3 (typically in an NO_x/NH_3 mol ratio of 1) is mixed with the flue gas prior to the activated carbon catalyst bed. The advantages of the proposed process concept compared to currently available SO_2/NO_x processes are summarized in Table 1.

Figure 1. Flue gas cleanup process concept.

Table 1. Advantages of Process

SO₂ Removal

● Easier retrofit	- Downstream of ESP where space is more readily available
● No waste product	- Sulfuric acid is potentially marketable
● Low temperature	- Reduced equipment stress, nonenergy intensive, no hazards including carbon combustion
● Simple regeneration	- No carbon loss
● Periodic operation	- Low pressure drop, concentrated sulfuric acid

NO_x Removal

● High catalyst life	- Low temperature operation in the absence of SO ₂ and particles significantly increases catalyst life
● Low salt/SO ₃ formation	- Due to complete SO ₂ removal upstream, the acid dew point of the gas is very low and salt formation is avoided
-

1.3 BACKGROUND

The SO₂ removal process proposed herein is based on the well-known low-temperature catalytic properties of activated carbon, but uses a novel periodically flushed trickle bed to produce a strong acid and a low level of SO₂ in the gas discharge. Hartman et al. (1971) and Hartman and Coughlin (1972) provide a detailed description of the mechanism of SO₂ oxidation [$\text{SO}_2 + (1/2)\text{O}_2 \rightarrow \text{SO}_3$ or $\text{SO}_2 + (1/2)\text{O}_2 + \text{H}_2\text{O} \rightarrow \text{H}_2\text{SO}_4$] over activated carbon. The SO₃ formed does not desorb spontaneously at low temperature. It is desorbed with water as sulfuric acid. Sulfuric acid, however, suppresses the ionization of dissolved sulfur dioxide and solubility of oxygen so that countercurrent contacting must be used to continue the reaction at an appreciable rate. Acid formation is accomplished in our process by periodic flushing, which results in a lower pressure drop and more concentrated sulfuric acid than achievable by continuous flushing.

Work in the co-principal investigator's laboratory at the University of Waterloo (Waterloo) (Haure et al., 1989) has shown the feasibility of the process. With a single bed and periodic water flushing (0.9 min water flow in every 90-min cycle), a time averaged acid concentration of nearly 0.2 molar was achieved. Based on this result, a conceptual process employing acid recycle to produce medium strength sulfuric acid is shown in Figure 2. SO_2 is absorbed from the gas phase and converted into sulfuric acid by two to three in-line periodically liquid-pulsed beds of carbon. Typically water, dilute strength acid or medium strength acid flows through them for 2 to 4 min in every 30- to 40-min cycle. The gas phase flows through the beds continuously. Co-current flow is employed so that high superficial velocities can be used without flooding. Two to three in-line, co-current trickle beds of sufficient depth should provide complete removal of SO_2 . The recycling arrangement passes the strongest acid through the bed, treating the richest gas, and thereby produces medium strength acid as a product. The gas-gas heat exchanger brings the flue gas leaving the third bed to the desired temperature for catalytic NO_x removal, which is the second part of our process, as shown previously in Figure 1.

Figure 2. Multistage activated carbon scrubbing process with pulsed liquid flow and cooling of the feed gas and reheating of the off-gas by heat recovery.

NO_x is reduced in a separate reactor at 120°C using NH_3 after the SO_2 has been removed, and the N_2 and H_2O are vented to the stack. One possible reaction is $4\text{NH}_3 + 4\text{NO} + \text{O}_2 \rightarrow 4\text{N}_2 + 6\text{H}_2\text{O}$, although many others are possible. Many catalysts for the NH_3 - NO reaction are reported in the literature (commercially practiced in selective catalytic reduction (SCR) technology using vanadium-based catalysts). However, many of these catalysts are inactive at 120°C . A comprehensive unpublished review of the literature by the principal investigators indicated that activated carbon or "coke" catalysts are the only catalysts with the potential to carry out the reaction at 120°C . Such catalysts are commercially used in the Mitsui process, which claims some 85% NO_x removal at 130°C . A number of studies (Kusakabe et al., 1988; Kuehl et al., 1986; Seki et al., 1975; U.S. Patent 4,194,373; Kareko et al., 1988) corroborate that activated carbons are active low temperature catalysts for the NO - NH_3 - O_2 and NO - NH_3 reactions. These studies further suggest that activated carbons promoted with very small quantities of group VIII transition metals (particularly platinum) should be considered.

1.4 PROJECT SCOPE/SCHEDULE

The novel carbon-based process to be studied has the potential to provide a technically sound and economically attractive solution to flue gas cleanup. The SO_2 removal experiments will be carried out in the apparatus of Haure et al. (1989) at Waterloo, modified to handle dilute to medium strength sulfuric acid and temperatures up to 100°C . The questions to be addressed in the research include:

- What acid concentrations are attainable by periodic pulsing and acid recycle?
- What is the pressure drop as a function of time during a cycle of no liquid flow to liquid flow?
- What is the optimum size of the granular activated carbon?
- What is the optimum pulse length to prevent poisoning (as occurring in steady-state operation) of the activated carbon?
- What is the optimal temperature of operation?
- What will be the effect and fate of NO_x ?

The experimental parameters investigated will include carbon type, size, bed depth, gas composition, liquid composition, gas velocity, liquid velocity, cycle time, flush time and gas temperature. To reduce the number of variables, the carbon used will be the BPL carbon (Calgon Corporation) which was found to be the most active in the previous study. Because the experiments are expected to be short, a large number of parametric experiments will be carried out to prove feasibility and obtain data to permit a process evaluation.

The NO_x removal experiments will be carried out at Research Triangle Institute (RTI). The experiments will be geared toward demonstrating >75% NO_x removal from off-gases expected from the activated carbon SO₂ conversion process. The principle variables considered will include carbon type (BPL carbon, 0.1 to 1% Pt on carbon, and three others), temperature (100 to 150°C), and space velocity [5,000 to 20,000 scf/(cf·h)]. A proper N₂ balance will be carried out in each experiment and slip of NH₃ and NO/NO_x in the reaction products will be measured. The effect of traces of SO₂ up to 250 ppmv on NO_x conversion will be examined.

Based on the experimental data, technical and economic evaluation of the process for 1 MW and 100 MW plants will be carried out. The technical evaluation shall determine the degree of SO₂ and NO_x removal that may be achieved in full-scale plants using the data collected in the controlled laboratory experiments. Economic evaluation will determine the cost of our process on unit power generation basis. The predicted cost will be compared with the cost of the conventional limestone flue gas desulfurization (FGD)/SCR system. If cost is at least 20% less for our process, our process will be considered for scaleup in future investigations.

The work to be carried out is divided into the following tasks:

<u>Task</u>	<u>Schedule</u>
Task 1: Program Definition (RTI and Waterloo)	June 4, 1991, to July 31, 1991
Task 2: Experimental 2.1: SO ₂ Removal (Waterloo) 2.2: NO _x Removal (RTI)	August 1, 1991, to February 28, 1993
Task 3: Process Evaluation (RTI)	May 1, 1992, to April 30, 1993

Task 1 (Program Definition) entails preparation of a detailed Project Management Plan describing a detailed work plan for the entire project and detailed test plans describing the experimental work. In Task 2 (Experimental), facilities will be constructed and experiments will be carried out per the approved Project Management Plan. SO₂ removal experiments will be carried out at Waterloo under the supervision of Dr. P.L. Silveston. NO_x removal experiments will be carried out at RTI under the supervision of Dr. S.K. Gangwal. In Task 3 (Process Evaluation), technical and economic evaluation of the process for 1 MW and 100 MW plants will be carried out by RTI.

It will be important to maintain a high degree of communication between Waterloo and RTI to ensure success of the project. The communication will be maintained by weekly conference calls. Also, an RTI investigator will travel to Waterloo at least twice during the project to review their experimental progress. Similarly, a Waterloo investigator will travel to RTI at least twice during the project.

1.5 MEASURES OF SUCCESS

The targets that we hope to achieve during the course of our experiments are:

- 95% or greater removal of SO_2 ,
- Production of at least 2 molar sulfuric acid,
- Pressure drop of at most 30 in. in the SO_2 removal process,
- 75% or greater removal of NO_x , and
- 25 ppmv or less NH_3 slip.

The experimental data would also indicate how to achieve further improvements in the above targets. The project is designed to prove the technical and economic feasibility of the process and provide sufficient data to permit a preliminary process evaluation. The ultimate test of the success of the project will be whether the process can reduce the cost of electricity over conventional FGD/SCR processes by 20%.

2.0 WORK COMPLETED IN PREVIOUS QUARTERS

The accomplishments in the previous quarters were as follows:

- Papers were presented at the Contractor's meetings and the Minneapolis AIChE meeting.
- Task 1 and 2 have been essentially completed.
- A number of promising catalysts have been developed and tested for both SO_2 removal and NO_x removal.
- Up to 99% SO_2 removal over multiple cycles and 85% NO_x removal has been demonstrated.
- An economic evaluation showed that the RTI-Waterloo process is competitive with SCR/FGD and other combined SO_2/NO_x processes.
- A paper was presented at the United States-Japan workshop.
- A paper was submitted to the Third International SO_2 removal symposium in Sheffield, England.

3.0 WORK COMPLETED IN PRESENT QUARTER

3.1 ACCOMPLISHMENTS

The accomplishments in the present quarter are as follows:

- Tests of 2 different catalysts were performed for SO₂ removal at 100°C.
- Tests of 5 different materials were performed for NO removal at temperatures ranging from 130°C to 160°C.
- A paper was presented at the Third International Desulfurization symposium in Sheffield, England. This paper is enclosed in Appendix 2.

3.2 SO₂ REMOVAL

3.2.1 SO₂ Removal Experiments at 21°C

See Appendix 1.

3.2.2 SO₂ Removal Experiments at Higher Temperatures

Two different catalysts were tested for SO₂ removal under conditions similar to those used previously for MCCI. The catalysts tested were MCCIV and MCCV. For each test, the reactor was loaded with 85cc of catalyst and operated at 100°C with a space velocity of 1508 scc/cc-h and a nominal SO₂ feed concentration of 2500 ppm.

In the first test cycle of the MCCV, 5% breakthrough occurred after 5 minutes on-line, after reaching a maximum removal of 98.8%. During the second test cycle, after rinsing the bed with 200 ml of 4.32N sulfuric acid, the highest removal achieved was 94.6%.

Testing of the MCCV produced a breakthrough time of 28 minutes during the first cycle, after reaching 98.3% removal, but only 82.3% removal was achieved during the second cycle.

Neither of these catalysts exhibited the high capacity for SO₂ removal which had been observed previously for MCCI. However, they are projected to be significantly cheaper than MCCI, so a trade-off exists. Additional high temperature (80°C) experiments were conducted at University of Waterloo who have now modified their continuous gas flow/periodic liquid flow test apparatus for 80-100°C operation.

3.3 NO_x REMOVAL

Several materials were tested for NO removal at temperatures ranging from 130°C to 160°C. These included activated alumina, platinum and nickel on alumina, carbon support, Pd on carbon, and MCCII. The materials tested are listed in Table 2.

Table 2. Catalysts Tested for NO Removal	
Catalyst #	Name
1	AAGI
2	PNAI
3	CIII
4	MCCIV
5	MCCII

The results of tests on these materials are summarized in Table 3. Very low NO conversion was observed for both Catalyst # 1 and 2. Catalyst III exhibited an NO conversion of approximately 5% at all temperatures tested. MCCIV produced NO conversions ranging from approximately 5 to 30% over the temperature range tested.

Tests of the MCCII catalyst were performed for comparison with previous testing of the same catalyst. The NO conversion of 90% at 140°C compared well with earlier tests which showed 86% conversion.

The purpose of these tests was to determine the effect of the combination of active metal species and catalyst support on NO conversion. The results will be used to develop a patent on the best catalysts.

During tests of catalyst #4 at 160°C, impinger samples of the outlet gas were collected for ammonia analysis and gas chromatography was used to analyze the nitrogen content of both the inlet and outlet gas streams. Based on these measurements and measurements of inlet and outlet NO concentrations, along with a calculated ammonia feed concentration, a nitrogen balance of 108.5% was determined. This indicated that no other side reaction products, such as NO₂ and N₂O are being formed in the RTI-Waterloo process. Note that SNCR and conventional SCR at high temperature, for example, may result in N₂O formation.

4.0 WORK PLANNED FOR NEXT QUARTER

4.1 SO₂ Removal

No activity planned.

4.2 NO_x Removal

No activity planned.

4.3 Process Evaluation

A final report will be prepared and a paper will be presented at the Contractor's meeting to complete the contract.

Table 3. NO_x Conversion Test Results

Catalyst	Bedsize (g)	Bed Vol. (cc)	Space Velocity (sec/cc.h)	Temperature (°C)	NO in (ppm)	NH ₃ /NO (nominal)	NO conversion (%)
1	52.6	85	1464	130	420	1.48	<5
1	52.6	85	1464	140	420	1.48	<5
1	52.6	85	1464	150	420	1.48	<5
1	52.6	85	1464	160	420	1.48	<5
2	40.6	56	2222	130	380	1.64	<2
2	40.6	56	2222	140	380	1.64	<2
2	40.6	56	2222	150	380	1.64	<2
2	40.6	56	2222	160	380	1.64	<2
3	35.6	85	1464	130	395	1.58	5.1
3	35.6	85	1464	140	395	1.58	5.1
3	35.6	85	1464	150	395	1.58	5.1
3	35.6	85	1464	160	395	1.58	5.1
4	37.6	85	1464	130	410	1.52	12.2
4	37.6	85	1464	140	410	1.52	4.9
4	37.6	85	1464	150	410	1.52	14.6
4	37.6	85	1464	160	410	1.52	29.3
5	40.2	85	1464	130	450	1.38	93.3
5	40.2	85	1464	140	450	1.38	90.0
5	40.2	85	1464	150	450	1.38	91.1
5	40.2	85	1464	160	450	1.38	92.2

5.0 REFERENCES

- Hartman, M., and R.W. Coughlin. 1972. *Chem. Eng. Sci.* 127:867-880.
- Harman, M., J. Polek, and R.W. Coughlin. 1971. *Chem. Eng. Prog. Symp. Ser.*, No. 115, 67:7-22.
- Haure, P., R.R. Hudgins, and P.L. Silveston. 1989. *AIChE Journal*, 35:1437.
- Kareko, K., Y. Nakahigashi, and K. Nagata. 1988. *Carbon*, 26(3):327-333.
- Keuhl, H., E. Richter, K. Knoblauch, and H. Juentgn. 1986. *Carbon '86*, Bergan-Forschung, Essen, Germany, pp. 351-353.
- Kusakube, K., M. Karhima, S. Morook, and K. Shigeharu. 1988. *Fuel*, 67(5):714-718.
- Seki, M., Y. Sakurai, and K. Yoshida. 1975. *Am. Chem. Soc. Div. Eng. Chem. Reprints*: 15(2), Chicago Meeting, August 24-29, pp. 28-31.

SKG:jw/2.5055MAR.QRT

APPENDIX 1
RECENT WORK AT
UNIVERSITY OF WATERLOO

80 °C Experiments

To carry out these experiments the equipment was modified as has been discussed in the fifth quarterly technical progress report. The experimental program was part of the sixth report.

It was anticipated from the RTI work that increased temperatures would lead to increased removal and conversion. The low temperature experiments were conducted because of contract requirements, to demonstrate that this process could work even at low temperatures, and to provide an estimate of the effect of temperature on process performance. There were a total of nine runs at 80 °C with several of these being duplicates. Table 3 of Appendix 1 in the sixth quarterly shows the variables employed. Table 1 below shows the level of the variables used in the four experiments and the measured responses for each experiment. For experiments R1, R2 and R4, the responses are averages of the results for individual runs.

Table1: Results of high temperature experiments

Exp. #	V _g	τ	A	C	% Remov.	% Conv.	[SO ₂] ⁻	[SO ₄] ²⁻
R1	-	-	-	-	67.07	66.79	8×10 ⁻⁵	1.99×10 ⁻²
R2	-	+	-	-	80.36	79.92	1.25×10 ⁻³	2.25×10 ⁻²
R3	+	-	-	-	25.71	25.52	1.7×10 ⁻⁴	2.29×10 ⁻²
R4	-	+	+	-	69.91	69.62	8×10 ⁻⁵	1.99×10 ⁻²

As is quickly apparent, removal and conversion are remarkably higher at 80 C. In contrast to the 20 C data in which conversions of SO₂ removed averaged 48%, 99% of the SO₂ removed from the gas stream is converted to sulfuric acid. With the exception of the one run at high gas velocity, SO removals ranged from 67 to 80% with the same 19 cm deep bed. At the high gas velocity the removal is about 5 times greater than the

removal at 20 C at this velocity.

Another effect is that increasing the cycle length from 30 to 60 minutes increased removal and conversion by about 10%. This is in line with Haure's results obtained at 25 C but with much higher SO₂ concentrations. It is an indication that SO₂ removal is controlled by mass transfer of oxygen to the catalyst surface so that reducing the liquid holdup increases the rate of oxygen transfer

At high gas velocities the removal and conversion were greatly reduced. This is expected and is consistent with all previous experimental results. It also appears that increasing the flushing liquid sulfuric acid concentration reduces the removal and conversion. Further experiments that will not be completed in time for the final report have been carried out using 5 molar acid at 80 C. These show that removals dropped to 10 to 20 % so that 5 molar represents the limiting acid strength that can be used for scrubbing at this temperature. These results confirm a strong effect of acid concentration on scrubber performance. The acid strength effect needs to be quantified. Behaviour with temperature also requires further study as to date we have just data at 20 and 80 C. To optimize this process, further experiments will be necessary.

In the course of these experiments, a substantial temperature drop in the scrubber was observed. It was thought initially that this was caused by thermal losses from the bed. To prevent this loss, two heating tapes were wrapped around the reactor bed, between the glass walls of the reactor and the insulation, and maintained at 80 C by thermocouples. These were mounted on the reactor walls. Despite this precaution, the temperature drop between the top of the bed and the bottom persisted. This difference, for some runs, reached 15 C. Temperature of the air and liquid entering the bed was very close to the design value of 80 C. Furthermore, during flushing, temperature in the bed quickly rose

to the design temperature. Occasionally, the top temperature reached 100 C. These observations demonstrate that the temperature drop results from evaporation of water retained in the bed after flushing is discontinued. Haure also observed this phenomenon in the experiments carried out at 20 C and 1.3% SO₂. The temperature rise mentioned above results from heat release due to dilution of the concentrated acid at the top of the bed. It is evident then that 80C the scrubber is acting as an acid concentrator. The simulated flue gas is not saturated at 10% water.

These experiments demonstrate convincingly that the scrubbing process should be operated at 80C or above. In our original three bed design it is now apparent that the top bed can be operated as an acid concentrator accepting flue gas at perhaps 10 to 20 C higher temperature. The two remaining beds can be combined into a single bed and if operated at 80 C or so, 98 - 99 % removal can be achieved. There are some very significant advantages resulting from these findings. It is now evident that acids up to 5 molar can be produced, but probably through concentration rather than absorption and reaction. The remarkable conversions mean that relatively shallow beds can be used at high gas velocities so that pressure drop will not be prohibitive. The water content of the flue gas is increased providing buoyancy for stack discharge. Finally, the higher operating temperature greatly reduces the size and cost of the heat exchange equipment. Indeed, if the NO_x process operating temperature can be reduced to between 80 and 100 C, reheating of the discharge from the SO₂ scrubber can be avoided. We are convinced that we are on the threshold of an outstanding stack gas clean-up process.

Comparing Periodic and Steady State Operation

Work undertaken through the auspices of a grant from the Canadian Natural Sciences Engineering and Research Council examined the steady state performance of the flue gas BPL activated carbon absorber. The results of the steady state work are consistent with the periodic data that has been conveyed to RTI in our previous quarterly reports. Steady state operation of the scrubbing system appears to give comparable SO_2 removals at the same time average liquid superficial velocity. Conversions to SO_3 were found to be higher. The difference between the two experimental systems in this study is the fact that under steady state operation the liquid flow over the reactor bed is continuous while in periodic operation the liquid flow is periodic. Both sets of experiments were conducted using the same equipment. The comparisons are between data collected when the liquid to flush the reactor was de ionized water as the steady state responses had the least amount of variability in this mode of operation. When 1molar acid was used as the flushing liquid the removals and conversions were found to be erratic

Figure 1 compares the percent removal of SO_2 versus superficial liquid velocity. For periodic operation the superficial liquid velocity is a time averaged value. Figure 1 is at a gas space velocity of 1000 scc/cc-hr and Figure 2 at 2850 scc/cc-hr. The steady state and periodic data appear to form a single data population. Both these figure show an increase in removal with an increase in liquid flow. It is evident that steady state operation achieves much higher removals. This is because normal liquid flow is much greater for periodic operation. Where the data overlap at a superficial velocity of 1mm/s, at low gas velocity and at roughly 7mm/s at high gas velocity the % removal under periodic operation is below that achieved at steady state. The spread of the low gas velocity data represent the effect of cycle period and flush duration. We conclude that the choice of period and duration were not optimal. At high gas velocities there is only one experimental point. Nevertheless, the data do not indicate that periodic operation is

superior to steady state at 20 C and with water as a flushing liquid.

The comparison of SO_2 conversion however is enigmatic. It was expected that without the continuous liquid flow there would be decreased mass transfer interference to the transport of SO_2 to the catalyst and that this would result in higher conversions for periodic operation. This was not seen. Figure 3 and 4 are for the low and high gas flow rates respectively. Once again steady state and periodic data are compared. At low gas velocity, a minimum in conversion with liquid superficial velocity is seen for the steady state data (Figure 3). This has been explained by Haure (1989) as follows, at low liquid velocities the catalyst is not completely wetted, therefore there is reduced mass transfer interference to SO_2 transport. As the liquid flow increases, there is increased mass transfer interference as more and more of the catalyst surface becomes liquid covered. At a certain point however, the mass transfer interference is reduced due to increasing liquid turbulence. At low gas velocity conversion for periodic operation are surprisingly lower than for steady state operation. We believe that this explained by non optimal choice of period and flush duration. Another possible explanation for the lower conversion than was expected with periodic operation is that the combination of low temperature and small liquid flow did not adequately remove the SO_3 formed on the catalyst surface due to channeling that is maldistribution of the liquid so that the catalyst was poisoned by the acid formed.

It can be seen from figure 3 that the minimum is not pronounced. The difference between this data and that collected by Haure is that measurements were made at between 0.8 and 2.2% by volume SO_2 in air (most were at 1.3%) and whereas SO concentrations were almost ten fold less in our present studies. On the other hand oxygen concentrations were only one quarter that used by Haure. We speculate that the less pronounced minima may have been the result of a shift in rate controlling step from

oxygen transport to reaction rate between the dissolved species.

In Figure 4 there is no minima in the steady state data; instead it appears that increasing the liquid flow rate increases conversion. Now the periodic and steady state data appear to be consistent. It should be noted that when the time averaged liquid velocity in periodic operation was increased above 6, a higher conversion was achieved which is in line with the steady state data points.

Figure 5 and 6 show the decrease in sulfuric acid concentration with increased liquid flow at low and high gas space velocities respectively. Both periodic and steady state data are shown and form a continuous curve. In these Figures, an advantage of periodic operation is evident. Much higher sulfuric acid concentrations can be achieved with periodic than steady state operation. In steady state operation, it is not possible to reduce the liquid flow below a certain point without the liquid flow becoming maldistributed and therefore reducing removal. With periodic operation a higher liquid flow can be used but since it is only for a short portion of the cycle, the time average liquid flow can be much lower than with steady state without maldistribution of the liquid.

Finally, Figure 7 and 8 are plots of sulfurous acid concentration versus liquid superficial velocity at low and high gas space velocities respectively. The steady state data seem to indicate that with increased liquid flow the concentration of sulfurous acid is reduced. The periodic operation data show no clear trend. The lower sulfurous acid concentrations for periodic operation are consistent with lower SO removals as seen in Figure 1 and 2. The reasons for this are explained above.

Removal vs. Liquid Velocity

Fig. 2

■ Periodic Operation * Steady State Data

Conversion vs. Liquid Velocity

Fig. 3

■ Periodic Operation * Steady State Data

Conversion vs. Liquid Velocity

Fig 4

■ Periodic Operation * Steady State Data

Sulfuric Acid Conc. vs. Liquid Velocity

Fig 5

■ Periodic Operation * Steady State Data

Sulfuric Acid Conc. vs. Liquid Velocity

Fig : 6

■ Periodic Operation * Steady State Data

Sulfurous Acid Concentration vs. Liquid Velocity

Fig 7

■ Periodic Operation * Steady State Data

The graph plots Sulfurous Acid Concentration (mol/L) on the y-axis against Superficial Liquid Velocity (mm/s) on the x-axis. The y-axis scale ranges from 0.001 to 0.006 with major grid lines every 0.001. The x-axis scale ranges from 0 to 8 with major grid lines every 1 unit. Two data series are plotted: one represented by asterisks (*) and another by squares (■). Both series show a general decrease in concentration as velocity increases, with some fluctuations.

Superficial Liquid Velocity (mm/s)	Sulfurous Acid Concentration (mol/L) (*)	Sulfurous Acid Concentration (mol/L) (■)
0.5	0.0057	0.0046
3.0	0.0031	-
3.5	0.0027	-
4.0	-	0.0022
6.5	0.0017	0.0016
7.0	0.0016	-

Fig. 8

APPENDIX 2
PAPER PRESENTED AT THE
DESULFURIZATION III SHEFFIELD CONFERENCE
MARCH 1993

LOW-TEMPERATURE CARBON-BASED PROCESS FOR FLUE-GAS CLEANUP

S.K. Gangwal*, W.J. McMichael*, G.B. Howe*, J.J. Spivey*, and P.L. Silveston†

* Research Triangle Institute, P. O. Box 12194, Research Triangle Park, NC 27709, U.S.A.

† University of Waterloo, Waterloo, Ontario, Canada N2L 3G1

A low-temperature process employing activated carbon-based catalysts and operating downstream of the electrostatic precipitator (ESP) is being developed jointly by Research Triangle Institute (RTI) and the University of Waterloo (Waterloo). The RTI-Waterloo process is capable of removing more than 95% SO₂ and 75% NO_x from coal combustion flue-gas. The feasibility of the process has been demonstrated in laboratory-scale experiments using simulated flue-gas. Cost for the RTI-Waterloo process was competitive with conventional selective catalytic reduction (SCR) - flue-gas desulfurization (FGD) process and other emerging combined SO₂/NO_x removal processes.

INTRODUCTION

Coal-fired power plants, with a total generating capacity of about 72,000 MW, account for approximately 68% of man-made SO₂ emissions in the United States. To meet New Source Performance Standards (NSPS), all new coal-burning plants require the installation of flue-gas desulfurization (FGD) units. Furthermore, new Clean Air Act amendments of 1990 will require retrofit FGD systems for many existing plants. Although the strict standards of air pollution control have resulted in the reduction of SO₂ emissions by nearly 30% in the last 15 years, a further reduction will be required. Pending legislation proposes to achieve 10 million tons of SO₂ reduction beyond the 1980 levels and 2 million tons of NO_x reduction by the year 2000. Low NO_x burners and advanced combustion-control techniques such as reburning can be used as a partial response for NO_x emission regulations. However, as in the case of FGD, a secondary NO_x treatment unit will be required to meet the strict emission control requirements.

This study is sponsored under the U.S. Department of Energy (DOE) Flue-Gas Cleanup (FGC) Program. The program has a goal to develop super-clean processes with potential to meet even more stringent regulatory requirements for coal-fired utility and industrial boilers than required by the year 2000. These super-clean processes aimed for application after the year 2000 must have the following attributes:

- 95% to 98% removal of SO₂, and 75% to 90% removal of NO_x from flue-gas streams
- Cost reduction of at least 20% compared to the combined cost of SO₂ and NO_x removal using a limestone scrubber and a selective catalytic reduction (SCR) process

- Production of salable byproducts in a process concept that produces no waste material.

The Research Triangle Institute-University of Waterloo (RTI-Waterloo) process is shown in Figure 1 and its advantages are summarized in Table 1. The hot flue-gas leaves the electrostatic precipitator (ESP) at $\sim 150^\circ\text{C}$ and enters a gas-gas heat exchanger to cool the flue gas for SO_2 removal and simultaneously heat the cold flue gas for NO_x removal. The gas leaving the exchanger enters a series of three activated carbon trickle-bed catalytic reactors at approximately 100°C . The SO_2 is catalytically converted to SO_3 and retained on the carbon catalyst. It is then removed by flushing periodically with sulfuric acid of desired strength. A novelty of the process is that a periodic rather than continuous liquid flush is employed which results in a higher strength acid product, a lower pressure drop, and greater activity for SO_2 conversion. The gas continues to flow through the bed at all times including during the periodic liquid flush. The gas containing less than about 25 ppm SO_2 from the last trickle-bed goes through the heat exchanger to the NO_x converter, also containing an activated carbon-based catalyst. The required amount of NH_3 (typically in an NO_x/NH_3 mol ratio of 1 to 1.5) is mixed with the flue gas prior to the activated carbon catalyst bed. In this bed, NO_x is reduced to N_2 and H_2O and then the clean flue gas is vented to the stack.

The objective of this paper is to demonstrate the preliminary technical and economic feasibility of the RTI-Waterloo process for removal of at least 95% SO_2 and at least 75% NO_x from coal combustion flue gas with less than 25 ppmv NH_3 slip. The work described below demonstrates the above and shows that the process has the

TABLE 1 - Advantages of Process

SO_2 Removal

• Easier retrofit	- Downstream of ESP where space is more readily available
• No waste product	- Sulfuric acid is potentially marketable
• Low temperature	- Reduced equipment stress, nonenergy intensive, no hazards including carbon combustion
• Simple regeneration	- No carbon loss
• Periodic operation	- Low pressure drop, concentrated sulfuric acid

NO_x Removal

• High catalyst life	- Low temperature operation in the absence of SO_2 and particles significantly increases catalyst life
• Low salt formation	- Due to complete SO_x removal upstream, the acid dew point of the gas is very low and salt formation is avoided

potential to produce concentrated sulfuric acid (via an additional evaporation step) at overall costs comparable to conventional SCR/FGD and other emerging SO_2/NO_x removal processes.

PROCESS BACKGROUND

SO_2 Removal

The RTI-Waterloo process is based on the demonstrated ability of activated carbon-based catalysts to promote SO_2 oxidation and NO_x reduction using NH_3 below 150°C . The SO_2 removal part of the process uses a novel periodically flushed cocurrent or countercurrent trickle-bed of an activated carbon-based catalyst to produce an acid product and low SO_2 levels in the gas discharge. Activated carbon is among the most efficient of all well-known oxidation catalysts (1). Use of activated carbons for stripping SO_2 out of gas streams has been studied extensively. It is not clear from the literature when the catalytic properties of activated carbon for the reactions $\text{SO}_2 + (1/2) \text{O}_2 \rightarrow \text{SO}_3$ or $\text{SO}_2 + (1/2) \text{O}_2 + \text{H}_2\text{O} \rightarrow \text{H}_2\text{SO}_4$ were first discovered. A detailed description of the mechanism of SO_2 oxidation over activated carbon is provided by various authors (2-4). Catalytic oxidation involves the reaction between SO_2 chemisorbed on active centers with chemisorbed molecular oxygen to form SO_3 which is then adsorbed on the surface and can be subsequently removed by washing with water or by heating to temperatures above 400°C (1).

Water plays an important role in the oxidation of sulfur dioxide over activated carbon (1). The presence of water vapor in the gas phase, together with oxygen and sulfur dioxide, increases the sulfur dioxide reactive capacity of a carbon bed. Sulfur dioxide oxidation is also favored by the presence of liquid water in the carbon at concentrations up to 0.3 g/g carbon (1). At low temperature, most of the sulfur trioxide formed is present at the surface of the catalyst as sulfuric acid. Sulfuric acid, however, suppresses the ionization of dissolved sulfur dioxide, decreasing its solubility. The solubility of oxygen in water is also reduced by the presence of sulfuric acid. The sulfuric acid thus must be removed to continue the reaction at a reasonable rate. By periodic flushing, the sulfuric acid is removed and the sites are regenerated for additional reaction.

The comprehensive review paper by Hartman et al. (2) reports preliminary experiments on stripping SO_2 from a simulated flue gas in both trickle-bed and slurry reactors. No attempt was made to optimize either the slurry or the trickle-bed process. Nevertheless, Hartman et al. achieved 70% SO_2 removal and generated a 0.1 M acid. Slurry contacting was pursued by Seaburn and Engel (5) and later by Komiyama and Smith (6). Seaburn and Engel were interested in comparing the performance of different activated carbons, while Komiyama and Smith were concerned with kinetics and mass transfer interference. They concluded that catalytic oxidation in a three-phase system is controlled by O_2 mass transfer rate to the surface. A thinner liquid film, as would be

achieved by periodic flushing in the RTI-Waterloo process, would result in a lower mass transfer resistance and consequently a higher oxidation rate.

The results of previous studies showed that the rate of oxidation of SO_2 to SO_3 and the formation of sulfuric acid vary greatly with the particular type of activated carbon used. Research on SO_2 adsorption and oxidation in a trickle-bed has continued since the Hartman-Coughlin work in the early 1970s. These include papers by Mata and Smith (7), Goto and Smith (8), Pavko and Levec (9), and Herskovitz (10). Although these investigators discuss the relevance of the work to flue-gas desulfurization, the main interest has been studying mass transfer and wetting in trickle-beds and development of theoretical models.

Work in the coauthor's laboratory at University of Waterloo began in the early 1980s and was directed at improving rates of reaction in trickle-beds by operating in the partially wetted state. Higher rates of mass transfer, it was reasoned, should raise the rate of reaction. Berruti et al. (11) explored the use of hydrophobic surface treatment, while Haure et al. (12) examined pulsing of the water flow. In both cases, SO_2 oxidation over activated carbon was used as the test reaction. The latter study led to the RTI-Waterloo process.

Haure's objective was to see if periodically starting and stopping liquid flow in a trickle-bed would raise the rate of reaction by reducing mass transfer resistance. SO_2 oxidation over activated carbon was used as a test reaction following the lead of previous investigators. The experimental results were remarkable: increases in the rate of oxidation of 40% to 60% were obtained. Although no optimization efforts were made, it was observed that moderately strong acid, almost 0.2 M, could be produced while still achieving a 40% to 60% increase in the oxidation rate at room temperature. This formed the basis for the RTI-Waterloo process. A patent has been obtained on the novel periodic operation feature of the process (Canadian Patent No. 1299843).

NO_x Removal

In the RTI-Waterloo process, NO_x is reduced using NH_3 at 130 to 150 °C in a separate reactor. SCR of NO_x using NH_3 is a proven catalytic process with numerous catalysts reported in the literature based on Fe, V, Cr, Mo, Co, Ni, Cu, Ba, and noble metals on alumina, titania, and silica supports (13-15). By far most of the literature deals with vanadia-based SCR catalysts. However, in nearly all cases, the catalysts described have been tested at temperatures much higher (200 to 400 °C) than of relevance to this study. One exception is the activated carbon or "coke" catalyst. Such a catalyst is used in the commercial Mitsui process and is active at 130 °C, converting some 85% of the NO_x at a space velocity of 400 h^{-1} (16). Since much of the SO_2 is removed before the NO - NH_3 reaction takes place, the Mitsui process catalyst, similar to the RTI-Waterloo process, does not have to promote this reaction in the presence of high levels of SO_2 . However, the space velocity of the Mitsui process is quite low presumably due to the low activity of the carbon catalyst employed. This results in large beds and thus high costs associated with the process. A significant incentive thus exists for finding more active low-temperature carbon-based (or other) catalysts.

A number of studies corroborate that activated carbons could be modified by impregnation or other surface treatment to increase their activity. Kusakabe et al. (17) studied the reduction of NO on activated coke catalysts which were modified by sulfuric acid treatment at 400 °C. This treatment increased the N₂ formation rate by up to 2.6 times that of the untreated catalyst. Kuehl et al. (18) showed that treatment by an "active nitrogen" increased the activity of the carbon catalyst. [Tests were carried out at 100 to 160 °C, 0 to 15% H₂O, 5% O₂, NO, and NH₃ concentrations below 100 ppm.] An ammonium oxide/carbon catalyst was found to be active for NO reduction using ammonia at temperatures as low as 100 °C (19). These same authors also described in a patent (U.S. Patent 4,184,373) the impregnation of carbon with halogens (Br, Cl, I) and a "promoter" to increase the activity of carbon for the NO-NH₃ reaction.

Other studies have dealt with the interaction of NO and NH₃, with various forms of activated carbon. The adsorption of NH₃ and NO, as single compounds, was measured by Kareko et al. (20) on activated carbon fibers prepared from pitch. At 30 °C, NO adsorption was 6 wt % at a partial pressure of 60 kPa, and NH₃ adsorption was 5 wt % at the same partial pressure, on the fiber having the highest capacity. Measurements at flue-gas concentrations around 200 ppm (0.15 kPa partial pressure) were not made, but the results suggest that NO and NH₃ have appreciable affinity for the carbon surface at low temperatures.

EXPERIMENTAL

Laboratory-scale experiments to demonstrate the RTI-Waterloo process were conducted using simulated flue gases (Tables 2 and 3). The SO₂ removal system consisted of 1.35 to 2.0 in. I.D. periodically flushed trickle-bed reactors through which simulated flue gas flowed continuously at the desired temperature. Water or dilute acid was employed for periodic flushing. The SO₂ was measured continuously using a UV-photometric analyzer.

TABLE 2 - SO₂ Removal Experiments Simulated Flue-Gas Composition

21 °C:	CO ₂ -	15 vol %	80 °C:	CO ₂ -	10 vol %
	O ₂ -	5 vol %		O ₂ -	5 vol %
	N ₂ -	Balance		N ₂ -	Balance
	SO ₂ -	600 to 2500 ppmv		SO ₂ -	2500 ppmv
	H ₂ O -	~2 vol %		H ₂ O -	10 vol %
				NO _x -	0 to 500 ppmv
130 °C:	Same as 80 °C				

TABLE 3 - NO_x Removal Experiments Simulated Flue-Gas Composition

10 vol %	H ₂ O
10 vol %	CO ₂
5 vol %	O ₂
0.05 vol %	NO
Balance	He

The NO_x removal system consisted of a 1.35 in.-I.D. packed-bed reactor. Simulated flue gases were generated using bottled gases and an NH₄OH solution of required strength was injected and vaporized into the flue gas to provide the desired amount of steam and NH₃. The NO_x was monitored continuously using a chemiluminescence analyzer and the NH₃ slip was measured by an impinger/ion-selective electrode.

RESULTS AND DISCUSSION

SO₂ Removal Experiments

SO₂ removal experiments were conducted at 21, 80, and 130 °C over three different activated carbon-based catalysts designated C1, C2, and modified carbon catalyst I (MCCI). The compositions of the catalysts are not disclosed pending determination of patentability.

The catalyst C1 tests involved exposure of the carbon bed to an SO₂-containing flue gas saturated with water at 21 °C for a certain time followed by a periodic water flush. The gas flowed through the catalyst continuously, even during the water flush. Cycle time was defined as the time period from the time of the start of a water flush to the start of a subsequent water flush. Liquid flush duration and cycle time were varied to attempt to find optimum points of SO₂ removal and acid strength produced. At a gas space velocity of about 1400 scc/(cc·h) with 2,500 ppm SO₂ in feed, only about 27% removal and about 6.5% conversion were obtained. To demonstrate, however, that 95% conversion could be achieved with a deeper bed or multiple beds, a series of experiments were conducted in which the inlet SO₂ concentration was reduced to a level where 95% conversion could be achieved. These results are shown in Figure 2 and show that more than 95% conversion is possible with a 600 ppmv inlet SO₂ under the same conditions.

Test of catalyst C2 involved cyclic exposure of the carbon-bed to an SO₂-containing flue gas containing 10 vol % H₂O and 2500 ppm SO₂ at 80 °C and 1400 scc/(cc·h) followed by liquid flush. During the first cycle, 99.3% removal of SO₂ was achieved. When the SO₂ concentration in the outlet rose to 5% of the inlet (i.e., 125 ppmv), the

85-cc catalyst bed was flushed with 200 cc of 4.3 N H_2SO_4 to obtain 4.5 N H_2SO_4 . The bed was then exposed to a second gas cycle. In this and subsequent cycles only 50% SO_2 removal was achieved even though the bed was washed with water in subsequent cycles. This indicated that some of the catalyst sites present initially had been irreversibly poisoned after the first cycle.

Most promising results were obtained with the MCCI catalyst, which was tested at 80 °C and 130 °C. A 10-cycle test was conducted on MCCI at 80 °C with 450 ppmv NO included in the simulated flue gas and with a flushing liquid acid strength of 4.32 N. The results of this test, shown in Table 4, indicate that the catalyst showed very high efficiency for SO_2 removal and exhibited very consistent behavior, especially over the last 8 cycles with about 7 g SO_2 converted per 100 g carbon prior to 5% breakthrough. In another 10-cycle test of MCCI at 80 °C, up to 9 N acid product strength was achieved by flushing with an 8 N acid. The catalyst showed no signs of permanent deactivation over the 20 cycles during the two tests.

For the run of Table 4, Figure 3 shows the reactor outlet gas temperature and SO_2 concentration as a function of cycle time for Cycle 6. The outlet temperature is lower than inlet due to evaporation of the water from the previous cold liquid flush. This appears to reduce the percent SO_2 removal during the time the bed heats up. To test this

TABLE 4 - SO_2 Removal Test Results (37.22 g of MCCI, 80 °C, 1.475 scc/(cc·h) Flue Gas Containing 2,550 ppm SO_2 , 450 ppm NO, 10% CO_2 , 10% H_2O , 5% O_2 , and Balance N_2 , Cold Flushing Liquid was 200 cc, 4.32 N H_2SO_4)

Cycle	Breakthrough time (h) ^a	Percent SO_2 Removal	SO_2 Converted (g) ^b
1	0.6	99.7	1.39
2	8.95	99.4	20.62
3	3.22	97.4	7.27
4	3.42	97.7	7.74
5	2.83	93.9	5.93
6	2.92	97.1	6.35
7	3.17	97.8	7.03
8	3.30	98.6	7.21
9	3.33	98.1	7.24
10	3.25	98.3	7.24

^a5% breakthrough.

^bPer 100 g carbon at 5% breakthrough.

hypothesis, a 3-cycle test was conducted on MCCI at 130 °C as opposed to 80 °C. As seen in Table 5, at this temperature although percent removal at the beginning was quite good, 5% SO₂ breakthrough occurred sooner.

However, the behavior seen at 80 °C as shown in Figure 3 was not observed at 130 °C. At 130 °C, the SO₂ removal started high (>95%) and remained high prior to the 5% breakthrough point. These results at 80 and 130 °C indicate that the optimum temperature of operation of the catalyst may be in between 80 and 130 °C, possibly around 100 °C. In any case, it appears feasible to obtain very high levels (in the high 90s) of SO₂ removal by the RTI-Waterloo process while producing medium strength sulfuric acid.

NO_x Removal

A number of activated carbon-based catalysts were procured/prepared and tested including a Carbotech lignite-based activated carbon which is used for the Mitsui process. Also, a Calgon bituminous coal-based activated carbon was tested. No details of other catalysts are reported pending determination of patentability. These included modified carbon catalysts I and II and C2. All catalysts tested were in form and size suitable for large-scale industrial operation.

The catalyst MCCI, which performed very well for SO₂ removal, was extensively tested for NO_x removal. The simulated flue gas shown in Table 3 was used for these tests. The NO_x removal data shown in Figure 4 were taken during a 267-hour longevity test of this catalyst. The catalyst showed no signs of deactivation after this long-term test. The data show that the required 75% NO_x removal with 25 ppmv or less ammonia slip can be obtained on this catalyst at a space velocity of 1300 to 1800 scc/(cc·h) [3000 to 4000 scc/(g·h)] at 135 to 145 °C with an NH₃ to NO_x inlet ratio of about 1.3. No NO₂ or other nitrogen products were detected in the outlet and the reaction suggested a stoichiometry in which 1.4 to 1.5 mol of NH₃ were consumed for every mol of NO feed.

TABLE 5 - SO₂ Removal Test Results (37.22 g of MCCI, 130 °C, 1,475 scc/(cc·h) Flue Gas Containing 2,550 ppm SO₂, 450 ppm NO, 10% CO₂, 10% H₂O, 5% O₂, and Balance N₂, 200 cc 4.32 N H₂SO₄ flush after each cycle)

Cycle	Breakthrough time (h) (at 5%)	Percent SO ₂ Removal	SO ₂ Converted (g)
1	1.75	99.6	3.83
2	0.8	97.8	1.67
3	1.1	99.7	2.32

MCCII was prepared by varying the promoter in MCCL. The results for this catalyst are shown in Table 6. Both these MCC catalysts appear to be capable of achieving the required performance of at least 75% NO removal at around 135 °C.

Looking further at data in Table 6 for MCCII, it is seen that ammonia slip and NO conversion are strong functions of the independent variables (space velocity, temperature and inlet NH_3/NO ratio). The first five data lines of Table 6 show essentially no NH_3 slip, i.e., the reaction is starved for NH_3 . As temperature is decreased a meager 5 °C at a space velocity of 1717 scc/(cc·h), ammonia slip increases from 6.2 ppmv to 121 ppmv but the NO conversion only drops by 5% from 88% to 83%. This suggests that NH_3 is not only consumed by reaction with NO but also by reaction with O_2 . Since no other nitrogen products (except N_2 itself) were observed in the effluent, it is concluded that some of NH_3 is oxidized to N_2 by O_2 in the gas and this reaction competes with the $\text{NH}_3\text{-NO}$ or $\text{NH}_3\text{-NO-O}_2$ reactions. Comparing the fifth data line of Table 6 with the last data line, it is seen that, with all other conditions constant as space velocity is nearly doubled from 1717 to 3354 scc/(cc·h), the NO conversion is hardly affected but the NH_3 slip increases significantly presumably due to the $\text{NH}_3\text{-O}_2$ reaction occurring to a lesser extent. This result indicates that the $\text{NH}_3\text{-O}_2$ reaction is much slower than the $\text{NH}_3\text{-NO}$ reaction. The data further indicate that it is very likely that NH_3 slip can be controlled to the desirable limit of 25 ppm at a space velocity of 3354 scc/(cc·h) by slightly increasing the bed temperature.

Finally, the performance of the MCCI and II and C2 catalysts are compared to Carbotech and BPL carbons in Figure 5. The results indicate the BPL carbon to be the worst performer. The MCCI and II and C2 catalysts perform significantly better than the Carbotech and BPL catalysts. The NO_x removal results demonstrate the feasibility of the RTI-Waterloo process to achieve the desired performance at space velocities of nearly 3500 scc/(cc·h).

TABLE 6 - Modified Carbon Catalyst II (MCC II) NO_x Removal Performance

Temp. (°C)	Space Velocity (scc/(cc·h))	Inlet NH_3/NO	NO Conversion (%)	NH_3 Slip (ppm)
140	1412	1.36	85.9	0.2
150	1414	1.36	87.9	0.2
130	1408	1.26	77.8	4.0
135	1408	1.26	81.5	0.8
135	1717	1.41	88.0	6.2
130	1717	1.41	83.0	121
140	3354	1.42	92.9	77.6
135	3354	1.42	87.9	220

ENGINEERING EVALUATION

Based on the results to date, a preliminary engineering and economic evaluation of the RTI-Waterloo process was conducted for a 100-MW electric power plant burning a 2.8% sulfur coal. The process and economic assumptions are shown in Table 7. The Electric Power Research Institute (EPRI) technical assessment guide (TAG) method was used for the calculations. An economic sensitivity analysis of the process with respect to the SO₂ conversion reactor variables (number of stages, catalyst cost, and catalyst life) was performed. In addition, sensitivity of the economics was performed for the acid product strength. It was assumed that the SO₂ reactors would yield 32 wt % H₂SO₄ and this was further concentrated using an external evaporator to 77.67 and 93.2 wt % H₂SO₄. The capital and levelized cost for this analysis is shown in Table 8 and compared to conventional and emerging SO₂/NO_x removal processes in Table 9. Even considering that the scale used for the RTI-Waterloo process was 100 MW as opposed to 500 MW for the other processes, the RTI-Waterloo process was competitive with the other processes.

TABLE 7 - Process and Economic Assumptions

Power Plant Capacity	--	100 MW, 65% Capacity Factor
Coal Type	--	Illinois #6, 2.8% Sulfur
Flue-Gas Composition	--	72.6% N ₂ , 4.5% O ₂ , 12.6% CO ₂ , 10% H ₂ O, 2300 ppm SO ₂ , 530 ppm NO _x
SO ₂ Conversion	--	2 or 3 Stages, 10,000 h ⁻¹ in each stage
NO _x Conversion	--	1 Stage, 3500 h ⁻¹ , NH ₃ /NO _x = 1.35, Promoted Carbon Catalyst, \$20/lb
Acid Storage	--	24 hours
Value of 32% H ₂ SO ₄	--	\$24/ton
Value of 77.67% H ₂ SO ₄	--	\$58/ton
Value of 93% H ₂ SO ₄	--	\$70/ton
Cost of NH ₃	--	\$150/ton
Dollars	--	Mid 1991

TABLE 8 - RTI-Waterloo Process Economic Performance (100-MW Power Plant, 65% Capacity Factor)

SO ₂ Conversion					
Stages (-)	Catalyst Cost (\$/lb)	Catalyst Life (yr)	Acid Product Strength (wt %)	Capital Cost (\$/kW)	Levelized Cost (mils/kWh)
3	20	3	32	179	8.2
2	20	3	32	162	6.8
3	20	3	77.67	188	9.0
3	20	6	77.67	188	7.3
2	20	6	77.67	171	6.4
3	20	6	93.2	188	8.3
2	20	6	93.2	171	7.4
3	3	2	77.67	169	6.3
3	3	2	93.2	169	8.0

TABLE 9 - Cost of SO₂/NO_x Removal (Mid 1991 \$)^a

Process	MW	Capital Cost (\$/kW)	Levelized Cost (mils/kWh)
Conventional FGD/SCR	500	200	8.8
Advanced FGD/SCR	500	170	7.8
NOXSO	500	215/260/300	8/11.8/17
SNOX	500	330/375/430	8.8/10.4/13
E-Beam	500	310/400/440	9/13.2/15.3
RTI/Waterloo	100	162 to 188	6.3 to 9.0

^aEstimates except for RTI/Waterloo process from reference 21.

CONCLUSIONS

The RTI-Waterloo process has been demonstrated at laboratory-scale to be capable of removing more than 95% SO₂ and more than 85% NO_x while producing a medium strength sulfuric acid product. Furthermore, a preliminary engineering evaluation shows potential for the process to be competitive with existing and emerging SO₂/NO_x processes. For future development, the process needs to be scaled up and tested with a slipstream of real flue-gas from a coal-fired boiler.

ACKNOWLEDGEMENT

This work was supported by the U.S. Department of Energy, Pittsburgh Energy Technology Center under Contract Number DE-AC22-91PC91345.

REFERENCES

1. Davtyan, O.K., and E.N. Ovchinnikova, 1955, Dokl. Akad. Nauk SSR, 104, 857.
2. Hartman, M., J. Polek, and R.W. Coughlin, 1971, Chem. Eng. Prog. Symp. Ser., 115, 67, 7-22.
3. Hartman, M., and R.W. Coughlin, 1972, Chem. Eng. Sci., 27, 867-880.
4. Siedlewski, J., 1965, Intern. Chem. Eng., 5, 297.
5. Seaburn, J.T., and A.J. Engel, 1973, Chem. Eng. Prog. Symp. Ser., 134, 69, 71.
6. Komiyama, H., and J.M. Smith, 1975, AIChE Journal, 21, 664.
7. Mata, A.R., and J.M. Smith, 1981, Chem. Eng. J., 22, 229.
8. Goto, S., and J.M. Smith, 1978, AIChE Journal, 24, 286.
9. Pavko, A., and J. Levec, 1981, Proc. 2nd World Congress of Chem. Eng. (Montreal), Vol. iii, 156.
10. Herskowitz, M., 1981, Chem. Eng. J., 22(2), 167.
11. Berruti, F., R.R. Hudgins, and E. Rhodes, 1984, Can. J. Chem. Eng., 62, 644.
12. Haure, P., R.R. Hudgins, and P.L. Silveston, 1989, AIChE Journal, 35, 1437.

ICHEME SYMPOSIUM SERIES NO. 131

13. Siddiqi, A.A., and J.W. Tenini, 1981, Hydrocarbon Processing, 60(10), 113.
14. Andersen, H.C., W.J. Green, and D.R. Steele, 1961, Ing. Eng. Chem., 53(3), 199-204.
15. Ayen, R.J., and A. Amirnazi, 1980, Ind. Eng. Chem. Proc. Des. Dev., 9(2), 247-254.
16. Mitsui Corporation, 1991, Private Communication with S. Gangwal of Research Triangle Institute.
17. Kusakabe, K., M. Karhima, S. Morook, and K. Shigeharu, 1988, Fuel, 67(5), 714-718.
18. Kuehl, H., E. Richter, K. Knoblauch, and H. Juentgn, 1986, Carbon '86, Bergbau-Forschung, Essen, Germany, pp. 351-353.
19. Seki, M., Y. Sakurai, and K. Yoshida, 1975, Am. Chem. Soc. Div. Env. Chem. Reprints, 15(2), 28-31, Chicago Meeting, Aug. 24-29.
20. Kareko, K., Y. Nakahigashi, and K. Nagata, 1988, Carbon, 26(3), 327-333.
21. Cichanowicz, J.E., et al., 1991, Engineering Evaluation of Combined SO₂/NO_x Removal Processes, Electric Power Research Institute.

Figure 1. RTI-Waterloo Process.

Figure 2. SO₂ Conversion to H₂SO₄ on Catalyst C1 at 21 °C and 1400 scc/(cc·h).

Figure 3. Outlet Temperature and SO₂ Concentration Versus Run Time (MCCI Catalyst, Inlet Temperature 80 °C, Cycle 6 of Table 4).

Figure 4. NO Conversion on MCCI (Space Velocity - 1370 scc/(cc·h) [3005 cc/(g·h)]; Inlet NO = 530 ppmv).

Figure 5. NO Conversion on Various Carbon-based Catalysts (85 cc bed; 1400 scc/(cc-h); 15.7 psia; 5% O₂, 10% CO₂, 10% H₂O, 75% inert; 530 ppm NO in; NH₃/NO = 1.26).

END

DATE
FILMED

7 / 19 / 93