**Evaluation of Products Recovered From
Scrap Tires for Use as Asphalt Modifiers**

Topical Report

J. McKay

Work Performed Under Contract No.: DE-FC21-86MC11076

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Western Research Institute
P.O. Box 3395
University Station
Laramie, Wyoming 82071**

May 1992

TABLE OF CONTENTS

	<u>Page</u>
LIST OF TABLES.....	iii
SUMMARY.....	iv
INTRODUCTION.....	1
EXPERIMENTAL.....	2
Materials.....	2
Procedures.....	2
RESULTS.....	4
Moisture Sensitivity Tests.....	4
Solid Carbonous Residues.....	8
Time Dependent Molecular Structuring.....	8
High Oil Content in CR Residue.....	10
CONCLUSIONS.....	12
ACKNOWLEDGMENTS.....	13
DISCLAIMER.....	13

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1. Summary of Moisture Sensitivity Tests Conducted Using Semi-Liquid or Solid Carbonous Products from Batch and Continuous Reactor Studies with Amoco AC-10 Asphalt: Duplicate Test Specimens.....	5
2. Effect of Solid Residues from CR Experiments on Modified Amoco AC-10 Asphalt: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive.....	8
3. Time Dependent Structuring Properties of Unaged Project Samples: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive.....	9
4. Time Dependent Structuring Properties of Laboratory-Aged Project Samples: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive; Oxidation Conditions: 163°C, 1.3 hours, 96 mL/minute Air, 8-g Sample.....	10
5. Effect of Oil-Free CR-9/10 Residue on Viscoelastic Properties of Amoco AC-10 and AC-20 Asphalts: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, WMO, 10 wt % Additive.....	11
6. Effect of Removal of Product Oil from CR-9/10 Residue on Rheological Properties of Modified Amoco AC-10 Asphalt: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive.....	11

SUMMARY

Western Research Institute performed rheological tests and water sensitivity tests on asphalt cements that had been modified with carbonous residues obtained from the pyrolysis of scrap tires and waste motor oil. These tests are part of an ongoing program at the University of Wyoming Chemical Engineering Department to evaluate, as asphalt additives, solid carbonous products recovered from the scrap tire and waste motor oil pyrolysis experiments conducted at the University. The tests showed that carbonous residues increased the viscosity and decreased the elasticity of AC-10 and AC-20 asphalts. The tests also indicated that asphalt cements modified with carbonous residues were less sensitive to water damage and age embrittlement than unmodified asphalt cements.

INTRODUCTION

Since January 1991 the Amoco Corporation and the University of Wyoming, Chemical Engineering Department (UW) have been involved in the first phase of a project to develop an advanced process for producing asphalt modifiers and light oil from scrap tires. The process uses shredded scrap tires together with waste motor oil, heavy vacuum bottoms, or refinery catalytically-cracked residuals to produce upgraded light oil, gas, and solid residue. Western Research Institute (WRI) and the U.S. Department of Energy (DOE) began jointly sponsored work on the project in July 1991. The role of Western Research Institute in this project has been to test and evaluate the solid residue from the process as a potential asphalt modifier. Asphalts modified with solid carbonous residue have undergone both rheological testing and water sensitivity testing at WRI. This report describes the results of the rheological and water sensitivity tests.

Results from preliminary testing conducted at WRI suggested that residual products produced from thermally degraded tires have merit as modifiers for asphalt cements (Plancher, H., University of Wyoming, Department of Chemical Engineering, personal communication, 1991). Asphalt cements modified with these residuals showed increased viscosity values and decreased elasticity values. They also flowed more easily under stress, age hardened at lower rates, and developed embrittlement more slowly than unmodified asphalts. Asphalt-aggregate test specimens containing carbonous-modified asphalt cements were less prone to moisture-induced damage than the corresponding control test specimens.

The jointly sponsored research involving DOE and WRI continued through May 1992. During this period samples of carbonous residuals produced from both batch and continuous reactors at UW were tested at WRI. Since the reactors and reaction conditions at UW were being optimized to produce a high quality carbonous residue and light product oil, the reaction products were of variable composition. These variations were primarily caused by entrained product oils in the recovered residues. Solvent extraction and thermal treatment of composite residue from the continuous reactor showed entrained product oil contents of 0.9 to 11.3 wt %. More recently, modifications of the 0.3 ton/day continuous reactor followed by additional heat treatments reduced the oil content of the solid residue to about 0.6 wt %. Modification of Amoco AC-10 asphalt with the relatively oil-free residue altered viscoelastic profiles to equal those initially obtained early in the project using the batch reactor. In general, the rheological and water sensitivity tests confirmed the results shown earlier.

EXPERIMENTAL

Materials

Solid Carbonous Residues from Continuous Reactor Experiments

Eight different solid carbonous residues from the single-stage, continuous bench-scale screw reactor (CR) experiments were utilized in product evaluation studies. Carbonous residues from nine different batch reactions (BR) were also tested. In the following tables, all runs up to Run 71 refer to batch experiments; all additional runs refer to continuous reactor experiments.

Aggregates

Various sized gravel particles from the Simon Pit near Cheyenne, Wyoming were obtained from the Materials Division, Wyoming Highway Department. This gravel when used in construction of asphaltic concrete roadways exhibits severe to moderate stripping problems (loss of asphalt film from aggregate surface after exposure to water). Aggregate RA is a granite from Grayson, Georgia. RJ is a mountain gravel conglomerate from Cheyenne, Wyoming. RH is a Greywacke siliceous aggregate from Pleasanton, California, and Porfido is a granite from Porfido, Italy.

Waste Oils

The waste oils used in the proprietary experiments to generate solid carbonous residues from scrap tires were from various sources. These included waste motor oils, heavy vacuum bottoms, refinery residuals, and aromatic (decant) oils. The identification of specific oils is proprietary and cannot be included in this report.

Procedures

Preparation of Sized Aggregate Particles

Approximately 3000 g of 20-35 mesh gravel particles were obtained by sieving two bags of aggregate fines. The sized particles were washed with tap water, rinsed several times with distilled water using a vacuum filtration procedure, and dried at 150°C (302°F). The aggregate, stored in a sealed glass bottle, was used for moisture sensitivity tests and for mechanical testing of briquette properties.

Rheology

Rheological measurements were made using a Rheometrics instrument, model RMS-605. Dynamic rheological properties were measured on project samples to evaluate changes in viscoelastic behavior of Amoco AC-10 and AC-20 asphalts modified with different solid carbonous residues. These measurements were made at 25°C (77°F) on a 2-mm asphalt film sandwiched between 25-mm parallel plates. Instrument parameters were 0.1 to 100 radians/second shear rate and 3% strain (amplitude of sine wave) with a 10 second delay before measurements at different shear frequencies. All measurements were initiated 2 hours after sample preparation procedures had been completed.

Sample Preparation

Sample preparation procedures consisted of placing a total of 17.5 g of asphalt or a 17.5 g mix of asphalt plus appropriate amounts of asphalt modifier(s) into a glass vial. The samples were mixed and annealed using a glass vial sealed with a cone-shaped Teflon stopper-cap assembly placed into a large aluminum block (thermal sink) heated to 150°C (302°F). Total heating time was 2 hours. At the end of each hour the aluminum block containing the glass vial was mechanically shaken for 5 minutes using a paint shaker. After final shaking, the vial was removed from the block and allowed to cool to ambient temperatures, without agitation, for 2 hours before commencing rheological measurements. Each sample (control or modified) was prepared individually to ensure that rheological measurements were made with the same elapsed time after sample preparation. All rheological data listed in this report are normalized to 50 g-cm torque (constant stress) to facilitate making comparisons between asphalt samples having varying consistencies.

Entrained Product Oils in CR-9/10 Residue

A 92-g sample of CR-9/10 residue (<200 mesh size) was extracted by Soxhlet procedure for 8 hours using freshly distilled dry benzene. The amount of benzene soluble material recovered represented 10.9 wt % of the CR-9/10 residue. A similar extraction procedure using 10 g of CR-9/10 residue and A.C.S. grade toluene resulted in a 14 wt % loss of soluble materials. The 3% difference between benzene and toluene extractions is believed to result from incomplete extraction of entrained oils in the larger, 92-g sample.

Thermal desorption of entrained oils from 200 g of CR-9/10 (70 mesh size) residue was conducted at 454°C (850°F) for 1 hour in the batch reactor with 100 mL/minute nitrogen sweep gas. This resulted in the recovery of 28.5 g of light product oil (14.3 wt %). The recovered solid residue was no longer in the 70 mesh range but rather in the 100 to 200 mesh range. Calcining the 100-200 mesh sample at 467°C (873°F) showed a 19.8 wt % loss. Recovered residue from the benzene Soxhlet extraction was used to prepare modified AC-10 and AC-20 asphalts containing 10 wt % carbonous residue. The modified asphalts were used in subsequent rheological and moisture sensitivity evaluations.

Moisture Sensitivity Tests

The sensitivity of asphalt-aggregate briquettes and asphalt-aggregate mixtures to moisture-induced damage (specimen failures or stripping of asphalt from the aggregate surface) were assessed using the freeze-thaw pedestal test. Various combinations of unmodified and modified Amoco AC-10 asphalts coated onto four different aggregates (two granitic and two siliceous) were evaluated.

RESULTS

Moisture Sensitivity Tests

Freeze-Thaw Pedestal Test

Data in Table 1 summarize all moisture sensitivity test results obtained on project samples since the beginning of the UW-Amoco Spent Tire project. Duplicate test specimens were prepared from unmodified and modified Amoco AC-10 asphalts and four different aggregates. Listed in the table are weight percentages of aggregate, modifier(s), and asphalt used to prepare each series of test specimens. Also listed in the table is the method by which modifiers were added, either directly to the asphalt, directly to the aggregate, or to both asphalt and aggregate. Additionally, the numbers of repeated freeze-thaw cycles required to induce specimen failure are shown. All test specimens containing calcium oxide or lime additions to the asphalt or aggregate showed significantly more cycles to failure, indicating reduction to moisture sensitivity. Moisture sensitivity evaluations were terminated after 50 repeated freeze-thaw cycles with no specimen failures. In the following tables WMO indicates waste motor oil, TGO indicates trim gas oil, and Microfilm-8 is a commercial carbon black that is used as an asphalt additive. RA identifies a Lithonia granite, RJ identifies a mountain gravel conglomerate, and RH identifies a Greywacke siliceous aggregate.

Table 1. Summary of Moisture Sensitivity Tests Conducted Using Semi-Liquid or Solid Carbonous Products from Batch and Continuous Reactor Studies with Amoco AC-10 Asphalt: Duplicate Test Specimens

Sample description	Cycles to failure
95% granitic (Porfido) aggregate + 5% AC-10	2
(94.75% Porfido + 0.50% WMO Slurry Oil, Run 10) + 4.75% AC-10	3
(94.79% Porfido + 0.96% WMO Slurry Oil, Run 10) + 4.25% AC-10	3
(94% Porfido + 1% WMO residue, Run 11) + 5% AC-10	3
95% RA granitic aggregate + 5% AC-10	1
(94% RA + 1% Microfilm-8 carbon black) + 5% AC-10	2
(93% RA + 1% Microfilm-8 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% pyrolyzed tires, Run 30) + 5% AC-10	1
(93% RA + 1% pyrolyzed tires, Run 30 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% pyrolyzed tires, Run 30) + (5% AC-10 + 1% Lime)	50+
(94% RA + 1% WMO, Run 33) + 5% AC-10	4,5
(94% RA + 1% WMO, Run 71) + 5% AC-10	2,3
(93% RA + 1% WMC, Run 71 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% WMO-CaO, Run 58) + 5% AC-10	7,9
(93% RA + 1% WMO-CaO, Run 58 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% TGO, Run 38) + 5% AC-10	1,2
95% RA + (5% AC-10 containing 10 wt % TGO, Run 38)	50+
(93% RA + 1% TGO, Run 38 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% TGO-CaO, Run 67) + 5% AC-10	50+
(93% RA + 1% TGO-CaO, Run 67 + 1% Lime) + 5% AC-10	50+
(94% RA + 1% BR-16) + 5% AC-10	2,3
(94% RA + 0.75% BR-16 + 0.25% Lime) + 5% AC-10	38,42
(93% RA + 1% BR-16 + 1% Lime) + 5% AC-10	50+
95% RJ siliceous aggregate + 5% AC-10	2,3
(94% RJ + 1% Microfilm-8 carbon black) + 5% AC-10	1
(93% RJ + 1% Microfilm-8 + 1% Lime) + 5% AC-10	50+
(94% RJ + 1% pyrolyzed tire, Run 30) + 5% AC-10	3,4
(94.5% RJ + 0.5% WMO Slurry Oil, Run 10) + 4.75% AC-10	2
(94.75% RJ + 0.25% WMO Slurry Oil, Run 10) + 4.50% AC-10	2
(94.25% RJ + 0.5% WMO Slurry Oil, Run 10 + 0.25% Lime) + 4.5% AC-10	18
(94% RJ + 1% WMO, Run 71) + 5% AC-10	3
(94% RJ + 1% WMO-CaO, Run 58) + 5% AC-10	10,11
(94% RJ + 1% TGO, Run 38) + 5% AC-10	2
(94% RJ + 1% TGO-CaO, Run 67) + 5% AC-10	50+
(94% RJ + 1% BR-16) + 5% AC-10	1,2
(94% RJ + 1% CR-6) + 5% AC-10	2
(94% RJ + 0.75% CR-6 + 0.25% Lime) + 5% AC-10	50+
(93% RJ + 1% CR-6 + 1% Lime) + 5% AC-10	50+

Table 1. Summary of Moisture Sensitivity Tests Conducted Using Semi-Liquid or Solid Carbonous Products from Batch and Continuous Reactor Studies with Amoco AC-10 Asphalt: Duplicate Test Specimens (continued)

Sample description	Cycles to failure
95% RH siliceous aggregate + 5% AC-10	7
(94.75% RH + 1% WMO Slurry Oil, Run 10) + 4.25% AC-10	17
(94% RH + 1% WMO, Run 11) + 5% AC-10	10
(94% RH + 1% TGO, Run 38) + 5% AC-10	9,11
(94% RH + 1% BR-16) + 5% AC-10	14
95% Simon Pit granitic gravel aggregate + 5% AC-10	5
(94% gravel + 1% CR-9/10) + 5% AC-10	6
95% gravel + (5% AC-10 containing 10 wt % CR-9/10 residue)	7,8
95% gravel + (5% AC-10 containing 10 wt % CR-11 residue)	7,8
95% gravel + (5% AC-10 containing 10 wt % CR-14 residue)	7
95% gravel + (5% AC-10 containing 10 wt % CR-17 residue)	7
(94% gravel + 1% CR-9/10 + 1% Lime) + 5% AC-10	>26

Porfido = granite aggregate from Italy
 RA = granite aggregate from Strategic Highway Research Program
 RJ = siliceous aggregate from Strategic Highway Research Program
 RH = siliceous aggregate from Strategic Highway Research Program

The Italian granite, Porfido, shown at the top of the table, is ideal for making cobblestones, but is totally unacceptable for use in bituminous concrete because of a severe stripping problem. Test specimens prepared from Amoco AC-10 asphalt and untreated granite particles fractured in two freeze-thaw cycles compared to three cycles for aggregate particles pretreated with WMO slurry oil or the WMO (Run 11) solid residue from the batch reactor experiments. Visual inspection of the fractured specimens showed severe loss of asphalt film from the aggregate surfaces. Doubling the amount of slurry oil (0.5 to 1 wt %) on the aggregate particles had no effect on test results.

The Lithonia granitic aggregate was evaluated for moisture sensitivity using a variety of project and non-project samples. Non-project samples included Microfilm-8 carbon black (a commercial asphalt modifier), calcium hydroxide, and pyrolyzed tire residue. In this series of moisture sensitivity evaluations most modifications were made to the aggregate.

Test specimens prepared from Amoco AC-10 asphalt with Lithonia granite or Lithonia granite modified with Microfilm-8 carbon black; pyrolyzed tire residue; or residues from WMO or TGO batch experiments or BR-16 residue from the continuous reactor all failed in less than three freeze-thaw cycles, except WMO, Run 33. These specimens broke on four and five cycles. The difference in moisture sensitivity results between WMO Runs 33 and 71 in the table might be attributable to the different heating profiles of the two batch reactors used in these experiments.

Moisture sensitivity test results show unmodified Amoco AC-10/Lithonia granite test specimens were more susceptible to moisture-induced damage than corresponding specimens prepared from Porfido aggregate. Calcium oxide additions to the retorting process or calcium hydroxide additions to the Lithonia aggregate resulted in test specimens lasting 50+ freeze-thaw cycles without failure. Even calcium hydroxide concentrations as low as 0.25 wt % of the aggregate (94% RA + 0.75% BR-16 + 0.25% calcium hydroxide) were found to be effective. This series of test specimens required 38 and 42 repeated freeze-thaw cycles to fracture the specimens. When calcium oxide was added to the retort process (Run 58) specimen failures occurred at seven and nine cycles. These preliminary results suggest the presence of carbonous residue on the surface of the calcium oxide may inhibit the antistripping properties of the oxide.

Two predominantly siliceous aggregates (Mountain conglomerate and Greywacke) were included in these moisture sensitivity tests. All Mountain conglomerate test specimens containing calcium oxide in the solid residue or calcium hydroxide-treated aggregate had marked increases in cycles to failure. TGO-CaO additions were more effective than WMO-CaO (Runs 58 versus 67). Comparisons between results show that Greywacke is more amenable to aggregate modification with solid carbonous residues than any of the five aggregates investigated. Moisture sensitivity tests with Simon Pit gravel show only slight increases in cycles to failure following additions of various CR modifiers to the asphalt.

Data in Table 1 show pretreatment of aggregates with residuals recovered from batch, BR, or continuous, CR, experiments can reduce the sensitivity of test specimens to moisture-induced damage. Some aggregates were beneficiated more than others, especially when either calcium oxide or calcium hydroxide was present. Calcium hydroxide additions to the aggregate were more effective than calcium oxide in the carbonous residue. Presently, there are insufficient data to determine whether the observed differences in cycles to failure relate to calcium oxide, calcium hydroxide, or to the presence of carbon on the oxide surface.

Solid Carbonous Residues

The effect on rheological properties of solid carbonous residues from CR experiments 2, 6, 7, 8, 9/10, 11, 14, and 17 mixed with Amoco AC-10 asphalt is shown in Table 2. Residue CR-11 was produced from decant oil and CR-14 and 17 residues were produced from WMO + CaO. All other residues were from WMO. Addition of each residue to the asphalt caused a decrease in viscosity. Viscosity decreases ranged from 44 to 72%. Comparison between WMO CR-9/10 and decant oil CR-11 residue modified asphalts shows the viscosity of the CR-11 sample is decreased 8% more than CR-9/10. This difference is attributed to the higher aromatic content of decant oil. Similar comparison between CR-7 and CR-17, the latter containing 10 wt % CaO, shows a 7% decrease after CaO addition.

Table 2. Effect of Solid Residues from CR Experiments on Modified Amoco AC-10 Asphalt: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive

Sample	G', dyne/cm ²	G'', dyne/cm ²	η^* , poise	Tan δ G''/G	% change η^*
AC-10	1.102x10 ⁵	5.173x10 ⁵	7.283x10 ⁵	4.694	---
AC-10+CR-2	1.058x10 ⁵	5.165x10 ⁵	2.031x10 ⁵	4.882	-72.1
AC-10+CR-6	1.122x10 ⁵	5.171x10 ⁵	4.077x10 ⁵	4.609	-44.0
AC-10+CR-7	1.245x10 ⁵	5.147x10 ⁵	4.041x10 ⁵	4.134	-44.5
AC-10+CR-8	1.175x10 ⁵	5.145x10 ⁵	3.585x10 ⁵	4.379	-50.8
AC-10+CR-9/10	9.595x10 ⁴	5.110x10 ⁵	3.441x10 ⁵	5.326	-52.8
AC-10+CR-11 ^a	1.042x10 ⁵	5.169x10 ⁵	2.918x10 ⁵	4.961	-60.0
AC-10+CR-14 ^b	9.713x10 ⁴	5.199x10 ⁵	3.233x10 ⁵	5.353	-55.6
AC-10+CR-17 ^b	1.094x10 ⁵	5.169x10 ⁵	3.515x10 ⁵	4.725	-51.7

^a = Decant oil, all others with WMO

^b = WMO + CaO

Time Dependent Molecular Structuring

Time dependent molecular structuring properties of Amoco AC-10 asphalt and AC-10 asphalt containing pyrolyzed tire or WMO residue (Run 11) are shown in Table 3. Dynamic rheological measurements were made at several time periods between 2 and 6528 hours after addition of pyrolyzed tire or WMO residue. The control AC-10 asphalt after a 4514 hour-cure at 25°C (77°F) in a sealed glass vial had a viscosity increase of 39% compared with a 43% increase

in viscosity for pyrolyzed tires and only a 2% increase in viscosity for the WMO residue modified AC-10 asphalt. After 6528 hour-cure the viscosity of the pyrolyzed tire modified asphalt had increased to 51% compared to 21% for the WMO residue modified asphalt. Insufficient amounts of the control sample precluded making a repeated measurement at 6500 hour-cure. A similar type of investigation conducted many years ago at WRI with commercial Microfilm-8 carbon black had results similar to those of the pyrolyzed tire residue. The viscosity results from the asphalt modified with WMO residue represent an important benefit for reducing the embrittlement process of a modified asphalt. The benefits of solid residue additions to asphalt may be further enhanced by additions of calcium oxide to the retorting process or by addition of calcium hydroxide to the asphalt.

Table 3. Time Dependent Structuring Properties of Unaged Project Samples: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive

Sample	Cure at 25°C, hours	G', dyne/cm ²	G'', dyne/cm ²	η*, poise	Tan δ, G''/G'	% change, η*
Amoco AC-10	2	1.216x10 ⁵	5.150x10 ⁵	7.802x10 ⁵	4.235	---
	1272	1.307x10 ⁵	5.412x10 ⁵	9.107x10 ⁵	4.141	16.7
	4514	1.232x10 ⁵	5.163x10 ⁵	1.086x10 ⁶	4.191	39.2
Amoco AC-10 + pyrolyzed tires	2	1.146x10 ⁵	5.178x10 ⁵	1.106x10 ⁶	4.518	---
	4513	1.159x10 ⁵	5.174x10 ⁵	1.580x10 ⁶	4.464	42.9
	6528	1.181x10 ⁵	5.184x10 ⁵	1.668x10 ⁶	4.390	50.8
Amoco AC-10 + WMO	2	1.152x10 ⁵	5.175x10 ⁵	1.206x10 ⁶	4.492	---
	4465	1.344x10 ⁵	5.393x10 ⁵	1.230x10 ⁶	4.013	2.0
	6526	1.334x10 ⁵	5.126x10 ⁵	1.457x10 ⁶	3.843	20.8

Similar time dependent molecular structuring measurements were obtained on laboratory-aged Amoco AC-10 asphalt and Run 11 WMO modified AC-10 after about 6200 hour-cure (Table 4). The percent increases in viscosity were 107 and 114%, respectively. These results indicate there is no apparent adverse effect from addition of a solid carbonous material (filler) to the asphalt. Both samples showed similar increases after aging and after prolonged cure.

Table 4. Time Dependent Structuring Properties of Laboratory-Aged Project Samples: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive; Oxidation Conditions: 163°C, 1.3 hours, 96 mL/minute Air, 8-g Sample

Sample	Cure 25°C, hours	G', dyne/cm ²	G'', dyne/cm ²	η*, poise	Tan δ, G''/G'	% change, η*
Amoco AC-10	2	1.407x10 ⁵	5.114x10 ⁵	1.990x10 ⁶	3.635	---
	6142	1.578x10 ⁵	5.078x10 ⁵	4.121x10 ⁶	3.218	107.1
Amoco AC-10 + WMO	2	1.374x10 ⁵	5.130x10 ⁵	2.568x10 ⁶	3.734	---
	6205	1.646x10 ⁵	5.254x10 ⁵	5.506x10 ⁶	3.193	114.4

High Oil Content in CR Residue

Soxhlet extraction of CR-9/10 residue with toluene readily showed the presence of soluble oil components, whereas similar extractions of batch Run 11 residue showed only trace amounts of oil being solubilized by the solvent. Additions of Soxhlet-extracted CR-9/10 residue described earlier in this report to Amoco AC-10 and AC-20 asphalts reduced the viscosity 34 and 38%, respectively (Table 5). This compares with 53% for the same residue before extraction (Table 2). Oil yield by the solvent extraction procedure for CR-9/10 residue was 11 wt %. However, when CR-9/10 residue was reprocessed in the batch reactor at 441°C (825°F) for 1 hour, oil yields approached 14 wt %. The viscosity values of the modified AC-10 asphalt containing batch reactor residue were similar to those obtained with Run 11 residue that has been considered as our target sample. Viscosity increases from original CR-9/10 modified AC-10 to thermally treated CR-9/10 residues ranged from 150 to 235% (Table 6). These increases corresponded well with reprocessing temperatures or residence times used in the 2-l batch reactor. Solid residue recovered from the reactor after termination of the CR experiments gave similar viscosity changes as Run 11 residue (150%), indicating that increased residence time at normal process conditions is sufficient to remove entrained product oils. As with previous batch reactor studies at the higher temperatures and longer residence times, the newly processed residues at the higher temperatures were less dispersible in the asphalt than those processed at the lower temperatures. Calcium hydroxide additions to the batch reactor experiments raised the viscosity value by 39% on Run 1. With Run 2 the increase was 57%.

Table 5. Effect of Oil-Free CR-9/10 Residue on Viscoelastic Properties of Amoco AC-10 and AC-20 Asphalts: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, WMO, 10 wt % Additive

Sample	CR-9/10 Treatment	G', dyne/cm ²	G'', dyne/cm ²	η*, poise	Tan δ, G''/G'	% change, η*
Amoco AC-10	none	9.595x10 ⁴	5.110x10 ⁵	3.441x10 ⁵	5.326	---
	Toluene Extracted	1.062x10 ⁵	5.179x10 ⁵	4.615x10 ⁵	4.877	34.1
Amoco AC-20	none	9.828x10 ⁴	4.937x10 ⁵	7.443x10 ⁵	5.023	---
	Toluene Extracted	9.990x10 ⁴	5.210x10 ⁵	1.024x10 ⁶	5.215	37.6

Table 6. Effect of Removal of Product Oil from CR-9/10 Residue on Rheological Properties of Modified Amoco AC-10 Asphalt: 25°C, 25-mm Parallel Plates, 3% Strain, 50 g-cm Torque, 10 wt % Additive

Residue Sample	Batch Reactor Conditions	G', dyne/cm ²	G'', dyne/cm ²	η*, poise	Tan δ, G''/G'	% change, η*
CR-9/10	Charge Sample	9.595x10 ⁴	5.110x10 ⁵	3.441x10 ⁵	5.326	---
CR-9/10	Run 1	1.159x10 ⁵	5.177x10 ⁵	8.656x10 ⁵	4.467	151.6
CR-9/10-Lime ^a	Run 1	1.192x10 ⁵	5.161x10 ⁵	9.972x10 ⁵	4.330	189.8
CR-9/10-Lime ^a	Run 2	1.153x10 ⁵	5.193x10 ⁵	1.062x10 ⁶	4.504	208.6
CR-9/10	Run 3	1.007x10 ⁵	5.193x10 ⁵	9.674x10 ⁵	5.157	181.1
CR-9/10	Run 4	1.064x10 ⁵	5.203x10 ⁵	1.078x10 ⁶	4.890	213.3
CR-9/10	Run 5	1.254x10 ⁵	5.189x10 ⁵	1.150x10 ⁶	4.138	234.2
CR-9/10	Residue Removed From CR Reactor	1.188x10 ⁵	5.173x10 ⁵	8.649x10 ⁵	4.354	151.4

^a = 10 wt % lime added to 70 mesh CR-9/10 solid residue, total charge to each batch reactor experiment was 200 g.

CONCLUSIONS

The rheological and water sensitivity tests confirmed the results shown earlier. Asphalt cements modified with carbonous residue showed increased viscosity values and a decrease in the storage modulus (G'). The loss modulus (G'') remained nearly constant with and without asphalt modifiers. An increase in G' is desirable to reduce pavement rutting. Moisture sensitivity tests with specimens containing solid carbonous residue and calcium oxide are significantly more tolerant to repeated freeze-thaw cycles than their corresponding controls.

ACKNOWLEDGMENTS

Appreciation is extended to the U.S. Department of Energy for funding of this work under Cooperative Agreement No. DE-FC21-86MC11076 and to Amoco for funding through the University of Wyoming. The author also thanks Mary Aldrich for conducting the moisture sensitivity tests and Felicia Reid for performing the rheological measurements.

END

DATE
FILMED

6 / 29 / 93