**High Voltage Research
(Breakdown Strengths of
Gaseous and Liquid Insulators)
Semiannual Report
(October 1, 1977-March 31, 1978)**

MASTER

OAK RIDGE NATIONAL LABORATORY
OPERATED BY UNION CARBIDE CORPORATION • FOR THE DEPARTMENT OF ENERGY

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Printed in the United States of America. Available from
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road, Springfield, Virginia 22161
Price: Printed Copy \$6.50; Microfiche \$3.00

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, contractors, subcontractors, or their employees, makes any warranty, express or implied, nor assumes any legal liability or responsibility for any third party's use or the results of such use of any information, apparatus, product or process disclosed in this report, nor represents that its use by such third party would not infringe privately owned rights.

Contract No. W-7405-eng-26
Activity No. C1 01 01 04 0

HEALTH AND SAFETY RESEARCH DIVISION

ATOMIC, MOLECULAR AND HIGH
VOLTAGE PHYSICS GROUP

HIGH VOLTAGE RESEARCH (BREAKDOWN STRENGTHS OF
GASEOUS AND LIQUID INSULATORS)

Semiannual Report
(October 1, 1977-March 31, 1978)

L. G. Christophorou

D. R. James
R. Y. Pai
R. A. Mathis
I. Sauers (Postdoctoral Fellow)
M. O. Pace (part time)
D. W. Bouldin (part time)
A. A. Christodoulides (alien guest)
C. C. Chan (student)

Date Published: June 1978

MASTER

NOTICE This document contains information of a preliminary nature. It is subject to revision or correction and therefore does not represent a final report.

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37830
operated by
UNION CARBIDE CORPORATION
for the
DEPARTMENT OF ENERGY

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

THIS PAGE
WAS INTENTIONALLY
LEFT BLANK

CONTENTS

	<u>Page</u>
Abstract	1
Breakdown Strengths of Multicomponent Gas Mixtures (Low Pressures)	3
Breakdown Strengths of Multicomponent Gas Mixtures (High Pressures)	5
Breakdown Strengths of Unitary Gases	13
Effect of Temperature on the Breakdown Voltage	16
Basic Studies: Continuation of Electron Attachment Measurements	20
The Role of the Electron Impact Ionization Cross Section on the Breakdown Strength of Dielectric Gases	27
Applied Studies	37
Impulse Studies	53
Environmental Aspects of Dielectric Gases	55
Apparatus	63
International Symposium on Gaseous Dielectrics	66
Visits and Contacts	67
References	68
Appendices	70

ABSTRACT

The work on gas mixtures is focusing on combinations of gases consisting of strongly electron-attaching components and one or more electron slowing-down components. Hypotheses based on the positions of electronically excited states are borne out experimentally in the low pressure (<1000 torr) breakdown measurements. The high pressure work shows dramatically the importance of the electron scattering cross section on breakdown strength by comparing Ar with Ne as single gases and in mixtures with SF₆. Although the ionization cross section for Ar is very much greater than that for Ne, Ar is a superior buffer gas.

A theoretical discussion is given which describes the relationship between the dielectric strength of a gas to its physical parameters including the electron attachment cross section, the ionization cross section, the ionization potential, and the electron energy distribution function. Also discussed is the importance of perfluorination in hydrocarbons to effect an increase in the electron attachment cross section and electron affinity and a decrease in the ionization cross section, and hence an increase in dielectric strength.

Attachment rates have been measured as a function of the mean electron energy for a comprehensive list of perfluorocarbons which include 1,3-C₄F₆, 2-C₄F₆, c-C₄F₆, c-C₅F₈, c-C₆F₁₀, C₆F₁₂, C₇F₈, and C₈F₁₆. Unfolded cross sections for electron attachment as a function of electron energy, $\sigma_a(\epsilon)$, were determined for c-C₅F₈, c-C₆F₁₀, and the three C₄F₆ isomers. These data show that perfluoro compounds have high $\sigma_a(\epsilon)$ up to 1.5 eV and that these are principally responsible for their high dielectric strengths.

Mixtures of SF₆, c-C₄F₈, 2-C₄F₈, and 2-C₄F₆ with N₂ have been examined,

in the cylindrical electrode geometry, for various inner cylinder radii and for varying degrees of roughness. The results indicate that the perfluorocarbons are less sensitive to field nonuniformity than SF_6 . There appear to be mixtures for which the breakdown strengths are virtually independent of surface roughness. Corona inception studies have begun, with the corona curve fitting the classical equation for corona in a concentric cylinder.

Breakdown voltages were determined for SF_6 and for $\text{SF}_6(20\%)/\text{N}_2(80\%)$ as a function of temperature from -15°C to 85°C . A 5-9% decrease in breakdown voltage is observed for the SF_6/N_2 mixture as the temperature is increased. The temperature range will be extended; further measurements on this and other systems are in progress.

Environmental aspects of gas dielectrics pertaining to gas decomposition and toxicity have been studied. Work has been completed on the initial fragmentation of the perfluorocarbons, $2\text{-C}_4\text{F}_6$, $2\text{-C}_4\text{F}_8$, and $\text{c-C}_4\text{F}_8$, and on the final decomposition of $2\text{-C}_4\text{F}_6$. The results indicate that $2\text{-C}_4\text{F}_6$ and $\text{c-C}_4\text{F}_8$ are relatively stable to electron impact over a wide energy range, while $2\text{-C}_4\text{F}_8$ is susceptible to extensive fragmentation even for ~ 0.0 eV electrons. Gases subjected to electrical stress are currently being studied.

I. BREAKDOWN STRENGTHS OF MULTICOMPONENT GAS MIXTURES (LOW PRESSURES)

The breakdown measurements on low pressure ($\lesssim 1000$ torr) multicomponent gas mixtures have been restricted during this reporting period to investigations of binary and tertiary mixtures of SF_6 and $2\text{-C}_4\text{F}_6$ with Ar and N_2 as the buffer gases. Argon was selected as a buffer gas primarily to determine the importance of excitation of high-lying electronic states on the breakdown voltage. We have already reported¹ on the effect of low-lying negative ion resonances (NIRs) on the breakdown voltage, V_S , for the buffer gases N_2 , CO, and H_2 . The studies on these three gases demonstrated the direct effect on V_S of the inelastic scattering properties of the gas via NIRs in the low-energy range (~ 1 to ~ 4 eV). It is important to extend these studies to investigate the role of higher-lying NIRs and the role of excitation of high-lying electronic states on V_S . Argon has two distinct sets of electronic states at ~ 11 eV and ~ 14 eV. If there is sufficient overlap of the electron energy distribution with the electron impact excitation cross section function for these, then the breakdown voltage of mixtures containing Ar should be affected. Table 1 shows the breakdown voltages of mixtures of the attaching gases SF_6 and $2\text{-C}_4\text{F}_6$ with Ar, N_2 and CO_2 as the buffer gases. The measurements were made at a total pressure of 500 torr using sphere-sphere electrode geometry. The N_2 mixtures were found to have substantially higher breakdown voltages than the corresponding Ar mixtures. The mixtures showed that N_2 is a better buffer gas than CO_2 which in turn is better than Ar. This could be an indication that excitation of higher-lying states is relatively unimportant. However there is some degree of synergism for the SF_6/Ar system. These studies (see also Section VI of this report)

are consistent with our earlier findings that the most important processes affecting V_S appear to be those in the subexcitation energy range, such as the NIR of N_2 at 2.3 eV.

Table 1. Relative breakdown voltages of mixtures containing Ar as a buffer gas

SF ₆	Percentage of component gas				$(V_S)_R^a$
	2-C ₄ F ₆	N ₂	Ar	CO ₂	
100					1.00
			100		0.12
10			90		0.32
10		45	45		0.52
10			45	45	0.42
10	10	70	10		0.86
20		40	40		0.60
20			40	40	0.51
20		70	10		0.72
40			60		0.57
40		30	30		0.76
40			30	30	0.67
40		50	10		0.83
40			10	50	0.73
		20	80		0.42
80			20		0.87
80		10	10		0.92

^aBreakdown voltage relative to SF₆; comparison made at $d = 0.325$ in and $P = 500$ torr; sphere-sphere electrode geometry.

II. BREAKDOWN STRENGTHS OF MULTICOMPONENT GAS MIXTURES (HIGH PRESSURES)

A large fraction of our work during this reporting period has been done in the "high" pressure regime (≥ 1000 torr). In our measurements we have tried, when possible, to cover a wide range of pressures, normally from 500 to 3500 torr. This procedure allows us to check for possible pressure dependences which may arise from physical processes and at the same time to investigate the dielectric strength properties at pressures comparable to those used in power apparatus (usually 4 to 5 atm).

Mixtures comprising SF_6 as the attaching gas with N_2 , Ar, and Ne as buffer gases have been investigated. Argon and Ne are particularly interesting to study as buffer gases because Ar and Ne differ dramatically in the magnitude of their electron-impact ionization and electron scattering cross sections. The significance of these cross sections and their relationship to breakdown voltage are discussed in Section VI.

We employed sphere on sphere to sphere electrodes (see Section X) in this work to achieve a more nonuniform electric field than with our sphere-sphere electrode geometry. Figure 1 presents the breakdown data on 40% Ar + 40% N_2 + 20% SF_6 and 100% SF_6 . The range of pressures used was from 500 to 3500 torr. At a given Pd, the breakdown voltage varies according to pressure. In general, the lower pressure will have the lower V_s at a constant Pd. This effect occurs because the low P will have a correspondingly larger d which makes the electric field more nonuniform and hence the breakdown voltage will be lower. The variation in the data at a constant Pd should not be construed as a genuine "pressure" effect but should be considered as an effect due to changes in the electric field configuration. The slight curvature of V_s vs Pd for a constant

Fig 1. Breakdown voltages, V_S , of 100% SF_6 and the mixture 40% Ar + 40% N_2 + 20% SF_6 at the indicated pressures (sphere on sphere-sphere electrode geometry).

pressure is also due to the changing electric field as the electrode separation, d , varies. As the field inhomogeneity increases the V_s of pure SF_6 is reduced much more than that of the mixture (see Fig. 1).

Figure 2 is a plot of V_s versus Pd for the mixture 40% Ne + 40% N_2 + 20% SF_6 . The electrode geometry was again sphere on sphere-sphere with pressures ranging from 500 to 3500 torr. The comments made with regard to the data in Fig. 1 on the variation of V_s with pressure also apply to the data in Fig. 2. Comparing the two mixtures we see that both are substantially lower in breakdown voltage than pure SF_6 and that the Ar mixture is approximately 10 to 13% higher in breakdown voltage than the Ne mixture. This observation is consistent with the data in Fig. 3 which show breakdown voltages at a constant pressure of 2000 torr for pure Ne and Ar as well as for 80% Ne + 20% SF_6 and 80% Ar + 20% SF_6 . The superiority of Ar as a single gas and as a buffer gas may be explained on the basis of the electron scattering cross sections as is discussed in Section VI.

Figures 4 to 6 give the breakdown voltage V_s for 40% Ar + 40% N_2 + 20% SF_6 , 40% Ne + 40% N_2 + 20% SF_6 mixtures and pure SF_6 as a function of the pressure P for fixed electrode gap separations of 0.125, 0.225, 0.325 in., respectively. For a fixed d , the nonuniformity in the electric field remains the same as the total pressure is increased. Generally, the data vary linearly with pressure up to 3000 torr. For the Ar mixture, beyond this pressure, the V_s falls off approximately 5 to 10% below the value one obtains from an extrapolated line through the rest of the data points. Considerably more scatter in the data occurs at the higher pressures (up to 1.5%) than at the lower pressures (scatter $\lesssim 0.5\%$) which is an indication of a higher overall uncertainty in the data at 3500 torr. Hence, the fall off at 3500 torr may not be a genuine pressure effect; it is most likely contained within the experimental error.

Fig. 2. Breakdown voltages, V_s , of 100% SF_6 and the mixture 40% Ne + 40% N_2 + 20% SF_6 at the indicated pressures (sphere on sphere-sphere electrode geometry).

Fig. 3. Breakdown voltages of pure Ne and pure Ar and respective mixtures with SF_6 ($P = 2000$ torr; sphere on sphere-sphere electrode geometry).

Fig. 4. Breakdown voltages of pure SF_6 , 40% Ar + 40% N_2 + 20% SF_6 and 40% Ne + 40% N_2 + 20% SF_6 as a function of pressure at a fixed gap distance (sphere on sphere-sphere electrode geometry, $d = 0.125$ in.).

Fig. 5. Breakdown voltages of pure SF_6 , 40% Ar + 40% N_2 + 20% SF_6 and 40% Ne + 40% N_2 + 20% SF_6 as a function of pressure at a fixed gap distance (sphere on sphere-sphere electrode geometry, $d = 0.225$ in.).

Fig. 6. Breakdown voltages of pure SF_6 , 40% Ar + 40% N_2 + 20% SF_6 and 40% Ne + 40% N_2 + 20% SF_6 as a function of pressure at a fixed gap distance (sphere on sphere-sphere electrode geometry, $d = 0.325$ in.).

III. BREAKDOWN STRENGTHS OF UNITARY GASES

The DC breakdown strength V_s of $c\text{-C}_4\text{F}_6$ (perfluorocyclobutene) has been measured and is shown in Fig. 7 along with those of other perfluorocarbons. The breakdown strength is approximately 1.7 times that of SF_6 . The breakdown strength of mixtures of $c\text{-C}_4\text{F}_6$ with N_2 have also been measured, and the results are shown in Fig. 8. After breakdown, $c\text{-C}_4\text{F}_6$ leaves a black deposit on the electrodes.

Concerning new gases we have been looking into the possibility of using perfluorinated amines (nitrogen containing compounds) as gaseous dielectrics. These have been studied at various times by the military in rocket propellant work, and the procedures for producing them might have not appeared in the open literature.

The specific compounds that we are interested in are not known to be toxic, and they have high vapor pressures at room temperature. If an efficient procedure for their production can be found we will ask a chemical company to synthesize them.

Fig. 7. Breakdown voltage, V_S , as a function of Pd for $c-C_4F_6$ compared with that for other unitary gases with vapor pressures ≥ 1 atm.

Fig. 8. Breakdown voltage, V_s , as a function of $c\text{-C}_4\text{F}_6$ in N_2 [$P_{\text{total}} = 500 \text{ torr}$; $P_d = 4.6 \text{ atm-mm}$; sphere-sphere electrode geometry].

IV. EFFECT OF TEMPERATURE ON THE BREAKDOWN VOLTAGE

The apparatus used for studying temperature effects on V_S has been described in detail previously.¹ The breakdown chamber can operate with pressures as high as 10 atm and with voltages up to 300 kV DC of either polarity. The present temperature range is $\sim -15^\circ\text{C}$ to $+85^\circ\text{C}$. We are in the process (see Section X) of expanding our capability to temperatures from $\sim -50^\circ\text{C}$ to $+150^\circ\text{C}$ which should cover the range of temperatures for practical uses.

Figure 9 gives the breakdown voltage, V_S , for pure SF_6 as a function of the temperature T for a fixed number density, N , of insulating gas. The data have been normalized to a number density of $0.50 \times 10^{20} \text{ cm}^{-3}$ which corresponds approximately to a pressure of 2 atm at 20°C . Data is now taken at standard gaps of 0.075, 0.125, 0.175, 0.225, 0.275, and 0.325 in. to facilitate comparisons. This normalization corrects for situations in which the gas had to be cycled while the chamber was at a temperature other than room temperature. The normalized Nd values are given to the right of the respective points in Fig. 9. As can be seen in the figure there does not appear to be a significant change in the breakdown voltage as the temperature is raised from -15°C to $+50^\circ\text{C}$ for pure SF_6 . At Nd values of 0.61 and $0.51 \times 10^{20} \text{ cm}^{-2}$ there is a slight decrease in V_S as T is increased, but it will be necessary to go to higher T to confirm this observation. We have plans to extend the upper temperature limit to $+150^\circ\text{C}$ in the near future to complete these studies.

Figure 10 is a plot of V_S vs T for a fixed number density of $1.24 \times 10^{20} \text{ cm}^{-3}$ which corresponds to ~ 5 atm at 20°C . These data have been normalized to that number density using the standard gap spacings. As

Fig. 9. Breakdown voltages for pure SF_6 as a function of temperature for fixed number density $N = 0.50 \times 10^{20} \text{ cm}^{-3}$ (plane-plane geometry) (see text for error estimate).

Fig. 10. Breakdown voltage for 20% SF₆ + 80% N₂ mixture as a function of temperature for a fixed number density of $1.24 \times 10^{20} \text{ cm}^{-3}$ (plane-plane electrode geometry) (see text for error estimate).

the temperature is increased from -1.4 to $+85^{\circ}\text{C}$ there is a noticeable decline in the breakdown voltage by $\sim 5\%$ to $\sim 9\%$ over the range of T covered. As a check of electrode condition and alignment which might be responsible for a reduced V_s , we remeasured the breakdown voltage at 20°C and obtained results consistent with previous measurements at that T . Again it is desirable to go to higher temperatures to verify these very interesting observations. These results and their interpretations are under study.

V. BASIC STUDIES: CONTINUATION OF ELECTRON ATTACHMENT MEASUREMENTS

In this period we have measured the electron attachment rates for $c\text{-C}_5\text{F}_8$ (perfluorocyclopentene) and $c\text{-C}_4\text{F}_6$ (perfluorocyclobutene) in N_2 and Ar and have unfolded the electron attachment cross sections as a function of electron energy for these compounds.

We have also measured the electron attachment rate for C_8F_{16} in Ar and thus extended the mean electron energy range over which the attachment rates were measured to 2.8 eV for this compound.

Figures 11, 12, and 13 show the electron attachment rates as a function of the mean electron energy, $\langle \epsilon \rangle$, for the three C_4F_6 isomers (Fig. 11), the $c\text{-C}_5\text{F}_8$ and $c\text{-C}_6\text{F}_{10}$ (Fig. 12) and the C_6F_6 , C_7F_8 and C_8F_{16} (Fig. 13) compounds. These attachment rates span two orders of magnitude for some of the compounds tested.

Figures 14 and 15 show the unfolded electron attachment cross sections as a function of electron energy for $c\text{-C}_5\text{F}_8$ and $c\text{-C}_6\text{F}_{10}$ (Fig. 14) and for the three isomers of C_4F_6 (Fig. 15).

All of the perfluoro compounds that we have studied show substantial attachment cross sections at higher (to ~ 1.5 eV) energies. This fact coupled with the high dielectric strength (1.4 to 2.4 times that of SF_6) points to the importance of capturing electrons with higher energies. (See earlier discussions in refs. 1 to 4).

We have submitted abstracts for two papers to be presented at the April, 1978, meeting of the American Physical Society in Washington, D.C. The abstracts are included in this report as Appendix I. Our work on the electron attachment cross sections of perfluorocarbons has reached a

ORNL-DWG 78-6834

Fig. 11. Electron attachment rate, αw , as a function of the mean electron energy, $\langle \epsilon \rangle$, for three ($c\text{-C}_4\text{F}_6$, $2\text{-C}_4\text{F}_6$ and $1,3\text{-C}_4\text{F}_6$) isomers of C_4F_6 . The maximum s-wave attachment rate $[\alpha w(\langle \epsilon \rangle)]_{\text{max}}$ is also shown on the figure.

Fig. 12. Electron attachment rate, αw , as a function of the mean electron energy, $\langle \epsilon \rangle$, for $c\text{-C}_5\text{F}_8$ and $c\text{-C}_6\text{F}_{10}$. The maximum s-wave attachment rate $[\alpha w(\langle \epsilon \rangle)]_{\text{max}}$ is also shown on the figure.

Fig. 13. Electron attachment rate, αw , as a function of the mean electron energy, $\langle \epsilon \rangle$, for C_6F_6 , C_7F_8 and C_8F_{16} . The maximum s-wave attachment rate $[\alpha w(\langle \epsilon \rangle)]_{\text{max}}$ is also shown on the figure.

Fig. 14. Swarm-unfolded electron attachment cross sections as a function of electron energy for $\text{c-C}_5\text{F}_8$ and $\text{c-C}_6\text{F}_{10}$. For comparison the electron attachment cross section for SF_6 and the maximum s-wave capture cross section, $\pi\lambda^2$, are also shown on the figure.

Fig. 15. Swarm-unfolded electron attachment cross sections as a function of electron energy for the three C_4F_6 isomers. For comparison the electron attachment cross section for SF_6 and the maximum s-wave capture cross section, $\pi\lambda^2$, are also shown on the figure.

stage at which we feel that we can synthesize the data and draw conclusions about the relationship of the attachment cross sections to the dielectric strengths of these compounds. We are preparing two papers on this subject to be submitted to the Journal of Chemical Physics.

VI. THE ROLE OF THE ELECTRON IMPACT IONIZATION CROSS SECTION ON THE BREAKDOWN STRENGTH OF DIELECTRIC GASES

We have indicated earlier¹⁻³ that in designing a gas dielectric the quantity

$$\int_0^{\infty} \sigma_a(\epsilon) f(\epsilon, E/P) d\epsilon \quad (1)$$

should be maximized, and the quantity

$$\int_I^{\infty} \sigma_i(\epsilon) f(\epsilon, E/P) d\epsilon \quad (2)$$

should be minimized. In (1) and (2) $\sigma_a(\epsilon)$ and $\sigma_i(\epsilon)$ are, respectively, the electron attachment and electron impact ionization cross sections, $f(\epsilon, E/P)$ is the electron energy distribution as a function of the electron energy ϵ and the pressure-reduced electric field E/P , and I is the ionization threshold energy. We have also emphasized in our earlier reports (e.g. 1-6) the dominant role of $\sigma_a(\epsilon)$ and the importance of the electron scattering processes which strongly influence $f(\epsilon, E/P)$. During this period we focused attention on the other basic parameter entering (1) and (2) namely $\sigma_i(\epsilon)$. From the dielectric point of view it is the portion of $\sigma_i(\epsilon)$ close to I which is the most significant. For multicomponent mixtures the role of the Penning ionization process ($A^* + B \rightarrow B^+ + e + A$) must be assessed also.

In the vicinity of I (say, 0 to ~ 10 eV of I) ionization proceeds directly

or indirectly,

Superexcitation (i.e., excitation of a neutral state above I) plays an important role for many molecules (e.g., see refs. 7 and 8). The competition between (3) and (4) is a function of $(\epsilon - I)$; as $(\epsilon - I)$ increases, (3) dominates over (4). The competition between indirect ionization (4a) and "dissociation" (4b) giving neutral fragments should depend on $(\epsilon - I)$, the state of excitation, and the vibrational distribution of internal energy and it could be beneficial in that it could reduce σ_i . Close to I the parent positive ions are the most abundant but as $(\epsilon - I)$ increases, so does the yield of fragment ions.

In Fig. 16 $\sigma_i(\epsilon)$ are plotted for a number of gases and are seen to vary greatly in the indicated energy range. A plot of σ_i vs $(\epsilon - I)$ (Fig. 17) shows a similar variation. If the values of σ_i for various species at a particular value of $(\epsilon - I)$ (say, 5 or 10 eV; Fig. 17) are plotted as a function of the species' static polarizability, α , σ_i increases with α , although the data show considerable spread. In the inset of Fig. 18 the slopes, $\Delta\sigma_i/\Delta(\epsilon - I)$, of the σ_i vs $(\epsilon - I)$ plots for $(\epsilon - I) \lesssim 2$ eV are plotted as a function of α . A general increase of $\Delta\sigma_i/\Delta(\epsilon - I)$ with α is evident. This is consistent with earlier data by Beran and Kevan⁹ some of which are shown in Fig. 18. For large values of ϵ the Born approximation is valid and one would expect σ_i to be proportional to α since both σ_i and α are roughly proportional to the square of the transition moment matrix element divided by the transition energy. Indeed a linear relationship between σ_i and α , as seen in Fig. 18, has been noted between $\sigma_i(\epsilon = 75 \text{ eV})$ and α earlier.^{9,10} At 75 eV the Born approximation is probably valid and direct ionization dominates over indirect for molecules. Beran and Kevan⁹ noted that the correlation

Fig. 16. Ionization cross section, σ_i , as a function of electron energy, ϵ , for He, Ne, Ar and a number of molecular systems [Based on the data of ref. 11].

Fig. 17. σ_i vs $(\epsilon - I)$ (see text).

Fig. 18. σ_i vs static polarizability, α , for the hydrocarbons CH₄, C₂H₆, C₃H₈, C₄H₁₀ and C₅H₁₂ and the perfluorocarbons CF₄, C₂F₆, C₃F₈ and C₄F₁₀ at three (20, 35, and 70 eV) electron energies. The σ_i values are from [9], the α -values for the alkanes are from [12] and the α -values for the perfluorocarbons are from [13] and were determined [13] using the method of [14].

Inset. $\Delta\sigma_i/\Delta(\epsilon - I)$ vs α . The $\Delta\sigma_i/\Delta(\epsilon - I)$ were determined for $(\epsilon - I)$ values $\lesssim 2$ eV using the $\sigma_i(\epsilon)$ data of [11] and I -values from [7]. The α -values are from [12] except for NO ($=19 \times 10^{-25} \text{ cm}^3$) which are from [15].

between σ_i and α holds better within given classes of molecules.

It is seen from Fig. 18 that for a given value of α , perfluorination of a hydrocarbon reduces $\sigma_i(\epsilon)$ and that this reduction is larger the lower the ϵ . This observation seems to be of quite general validity (see Table 2 and ref. 9).

Additionally, as can be seen from Table 3, the I of perfluorinated hydrocarbons is, as a rule, higher than for their nonfluorinated analogues. Quite generally, when an F atom is substituted for an H atom, $\sigma_i(\epsilon)$ decreases. The other halogen atoms (Cl, Br, I) do not behave in this manner; for these, $\sigma_i(\epsilon)$ increases with increasing number of halogens and atomic number (i.e., in the order $\text{Cl} < \text{Br} < \text{I}$) (see Table 2 and ref. 9). This behavior indeed reflects the unique properties of the ground state F atom [the electronegativity (4.0) and I (17.42 eV) of fluorine are very high] allowing for strong C-F bonds, tightly bound electrons and low-lying negative ion states. It is thus seen that perfluorocarbon molecules possess very large $\sigma_a(\epsilon)$, low $\sigma_i(\epsilon)$, high I, and positive (and often large) EA, all of which are desirable basic properties for a dielectric.

To assess the role of $\sigma_i(\epsilon)$ relative to $\sigma_{sc}(\epsilon)$ --and thus the relative significance of (1) and (2)--we have chosen four gases for which $\sigma_i(\epsilon)$ and $\sigma_{sc}(\epsilon)$ are known (Fig. 19, A, B). Measurements of the DC breakdown strength of Ar, Ne, Ar + SF₆, Ne + SF₆, N₂ + Ar + SF₆, N₂ + Ne + SF₆ (see Section II, Table 4 and Fig. 19) show that Ar is superior as a buffer gas to Ne in spite of the fact that $I_{\text{Ar}} < I_{\text{Ne}}$ and $(\sigma_i)_{\text{Ar}} \gg (\sigma_i)_{\text{Ne}}$ (Fig. 19A). This is attributed to the differences in $\sigma_{sc}(\epsilon)$ between Ar and Ne shown in Fig. 19B: Argon is a much more efficient electron

Fig. 19. A. $\sigma_i(\epsilon)$ for Ar, SF_6 , N_2 and Ne [data from Ref. 11].
 B. Electron scattering cross section as a function of ϵ .
 N_2 : total electron scattering cross section, σ_t , [17];
 momentum transfer cross section, σ_m , [18].
 SF_6 : σ_t [19]; σ_m [20].
 Ar: σ_t [21].
 Ne: σ_t [22].

Table 2. Ionization cross sections, σ_i , at three (20, 35 and 70 eV) electron energies for hydrocarbons showing the effect of fluorine and other halogen atoms on σ_i ^a

Molecule	σ_i (10^{-16} cm ²)		
	$\epsilon = 20$ eV	$\epsilon = 35$ eV	$\epsilon = 70$ eV
CH ₄	1.62	3.65	4.67
CH ₃ F	1.27	3.03	4.46
CH ₂ F ₂	0.94	2.75	4.56
CHF ₃	0.55	2.41	4.47
CF ₄	0.26	2.22	4.68
C ₂ H ₆	3.32	6.45	8.51
C ₂ F ₆	0.61	3.89	7.79
C ₃ H ₈	4.79	8.91	11.5
C ₃ F ₈	1.07	5.52	10.5
C ₄ H ₁₀	6.45	11.4	15.3
C ₄ F ₁₀	1.62	7.25	13.5
C ₃ H ₆			10.2
C ₃ F ₆			9.16
2-C ₄ H ₈			13.9
2-C ₄ F ₈			12.2
C ₂ H ₄			6.93
C ₂ F ₄			6.16
CH ₃ F			4.46
CH ₃ Cl			8.68
CH ₃ Br			10.1
CF ₄	0.26	2.22	4.68
CF ₃ Cl	2.02	5.15	7.79
CF ₃ Br			9.07
CF ₃ I			10.9
CF ₄	0.26	2.22	4.68
CF ₂ Cl ₂	4.2	8.52	11.2
CF ₂ Br ₂			14.2
CFCI ₃	6.26	11.7	14.6

^a From ref. 9.

Table 3. First ionization potential, I, of hydrocarbons showing the effect of F substitution on the value of I ^a

Compound	I(eV)
CH ₄	12.7
CH ₃ F	12.54
CH ₂ F ₂	12.71
CHF ₃	13.83
CF ₄	≤15.0
<hr/>	
C ₃ H ₈	11.07
C ₃ F ₈	13.38
<hr/>	
2-C ₄ H ₈	9.13
2-C ₄ F ₈	11.25
<hr/>	
c-C ₃ H ₆	9.97
c-C ₃ F ₆	11.3
<hr/>	
C ₅ H ₁₀ (cyclopentane)	10.5
C ₅ F ₁₀	11.7
<hr/>	
C ₆ H ₁₂ (cyclohexane)	9.83
C ₆ F ₁₂	13.2
<hr/>	
C ₆ H ₆ (benzene)	9.24
C ₆ F ₆	9.93
<hr/>	
C ₁₂ H ₁₀ (biphenyl)	8.23
C ₁₂ F ₁₀	10.00
<hr/>	
C ₂ H ₄	10.51
C ₂ H ₂ F ₂	10.31
C ₂ HF ₃	10.14
C ₂ F ₄	10.12
C ₂ Cl ₂	11.4
C ₂ F ₂	11.4

^aData on I from refs. 5 and 16.

Table 4. V_s for SF_6 , Ar, Ne, $SF_6 + Ar$, $SF_6 + Ne$, $SF_6 + Ar + N_2$ and $SF_6 + Ne + N_2$ ($P_{total} = 2000$ torr; sphere on sphere-electrode geometry)

Gas/Mixture	Electrode Separation (inches)				
	0.125	0.225	0.325	0.425	0.525
	V_s (kV)				
$SF_6(100\%)$	41.40	60.31	77.21	92.61	
Ar(100%)	5.38	7.73	9.70	11.41	14.09
Ne(100%)	0.93	1.32	1.55	1.95	2.46
$SF_6(20\%) + Ar(80\%)$	20.38	29.00	35.91	43.48	54.29
$SF_6(20\%) + Ne(80\%)$	13.56	21.04	28.37	35.49	48.40
$SF_6(20\%) + Ar(40\%) + N_2(40\%)$	27.76	40.29	50.40	59.11	79.19
$SF_6(20\%) + Ne(40\%) + N_2(40\%)$	24.43	35.70	44.97	52.77	74.17

slowing-down gas than Ne. The results on the V_s for the tertiary mixtures further substantiate this contention: when N_2 (for which $\sigma_{sc}(\epsilon)$ is large at subexcitation energies; Fig. 19B) is added to the $SF_6 + Ne$ mixture, the V_s improves much more than when it is added to the $SF_6 + Ar$ mixture.

These findings are consistent with earlier observations¹⁻⁴ and demonstrate the significance of efficient electron scattering at subionization energies. They indicate that large electron scattering cross sections in the subionization ($\epsilon < I$) and subexcitation ($\epsilon < \text{energy of lowest excited electronic state}$) energy range are more important than low $\sigma_i(\epsilon)$.

VII. APPLIED STUDIES

Studies of the gases SF_6 , $\text{c-C}_4\text{F}_8$ (perfluorocyclobutane), $2\text{-C}_4\text{F}_8$ (perfluorobutene-2) and $2\text{-C}_4\text{F}_6$ (perfluoro-2-butyne) and their binary mixtures with nitrogen have continued in the practical test facility with concentric cylinder geometry. This apparatus has been described in the last report.¹ The new Delta Ray power supply for higher voltages, originally expected in November, 1977, did not arrive in time for use this period.

The breakdown measurements in concentric cylinder geometry have been almost completed for the above four gases and their binary mixtures with nitrogen for the concentric cylinder geometries where the ratio of electrode radii is $0.5 e$, e , and $2 e$ (where e is the basis of natural logarithms). The previous data of this type were given in Figs. 9 through 13 of ref. 1; the remaining data of this type are now presented in Figs. 20 through 23. In these figures each data point is the mean of at least ten breakdowns with random scatter (standard deviation $\div$ mean $\times 100$) of less than 3%. The data for $2\text{-C}_4\text{F}_6$ are not complete. There is need for additional data at higher voltages; these will be obtained when our new Delta Ray power supply is received.

The breakdown data in Figs. 20 through 23 for $\text{c-C}_4\text{F}_8$ and $2\text{-C}_4\text{F}_8$ show that the saturation effect exhibited by the SF_6/N_2 mixtures is diminished in the more nonuniform fields and is essentially absent for these perfluorocarbons, as suggested in our last report.¹ If one examines the relative behavior of each of the four gases as the cylinder field becomes progressively nonuniform in going from 1.4 to 0.4 cm inner cylinder radius the breakdown voltage ratios indicate that SF_6 is slightly

Fig. 20. Breakdown voltages for c-C₄F₈/N₂ mixtures with cylindrical electrode radii of 1.4 and 2 cm. ($\circ$) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data.

ORNL-DWG.78-8873

Fig. 21. Breakdown voltages for 2-C₄F₈/N₂ mixtures with cylindrical electrode radii of 0.4 and 2 cm. (o) inner electrode at positive potential, (●) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 22. Breakdown voltages for 2-C₄F₈/N₂ mixtures with cylindrical electrode radii of 0.75 and 2 cm. (o) inner electrode at positive potential, (●) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 23. Breakdown voltages for 2-C₄F₈/N₂ mixtures with cylindrical electrode radii of 1.4 and 2 cm. (o) inner electrode at positive potential, (●) inner electrode at negative potential, (Δ) normalized uniform field data.

more sensitive to these degrees of field nonuniformity than are the other gases. It can also be seen that the breakdown voltages are higher on the 0.75-cm radius electrode than on the others, because that radius provides the minimum E field at the inner electrode surface (the inner radius is $1/e$ of the outer radius). The effects of field fringing at the open ends of the concentric cylinder geometry are revealed by the fact that breakdown voltages for the 0.4-cm radius electrode are almost as high as those for the larger, 0.75-cm radius, electrode. This occurs because fringing weakens the field more for smaller inner cylinders due to the more open area at the cylinder ends.

Studies have also been made of corona inception by two methods: (1) calculate corona current from pulse heights observed on the partial discharge detector and pulse rates observed on a storage oscilloscope, and (2) measure average current by observing the voltage on a resistor carrying corona current to ground from the outer cylinder. The former method gives greater sensitivity and provides visual detail on the corona pulse character, but the latter method excludes corona elsewhere in the system besides the actual inter-electrode region. The study of these methods will resume after suspected sources of stray corona are eliminated (the power supply and air terminal corona guard are being replaced by improved hardware). Corona current characteristics of various mixtures will be obtained to link gas decomposition studies in corona with conditions of corona in practical geometries.

Figures 24 through 26 present examples of the data obtained on corona current vs voltage. The curves in Figs. 24 and 25 fit reasonably well the classical equation for corona in concentric cylinders, $I = KV(V-V_0)$

Fig. 24. Corona current in 2-C₄F₆ vs voltage with cylindrical electrode radii of 0.11 and 2 cm, calculated from corona pulse heights and rates. (o) inner electrode at positive potential, (●) inner electrode at negative potential.

Fig. 25. Corona current in $2-C_4F_8$ vs voltage with cylindrical electrode radii of 0.75 and 2 cm, calculated from observed corona pulse heights and rates. (○) inner electrode at positive potential, (●) inner electrode at negative potential.

Fig. 26. Corona current in a SF₆/N₂ mixture vs voltage, with cylindrical electrode radii of 0.4 and 2 cm, measured in ground lead resistor. (○) inner electrode at positive potential, (●) inner electrode at negative potential.

where I = corona current, V = applied voltage, V_0 = inception voltage and K is a constant. The current measurements in Figs. 24 and 25 have errors estimated to be $\pm 10\%$. These curves are typical of those so far obtained in that the inception voltage is lower with positive polarity, and the slope of the I vs V function is greater with negative polarity. The curves in Fig. 26 are typical of measurements made by observing the voltage on a resistor carrying corona current to ground. The current measurements in Fig. 26 have errors estimated to be $\pm 5\%$. These methods will be studied further after the air terminal corona guard and power supply are replaced.

Studies of the effects of inner-cylinder surface roughness have begun also. Figures 27 through 30 present breakdown data for SF_6/N_2 mixtures and $\text{c-C}_4\text{F}_8/\text{N}_2$ mixtures on two inner-cylinder electrodes, both of 0.75 cm radius but each with a different degree of roughness. Each of these breakdown voltages is the mean of at least ten measurements with random error (standard deviation $\div$ mean $\times 100$) of less than 3%. These two degrees of roughness were chosen such that the lesser was anticipated to have little effect on SF_6 at 1 atm and the greater roughness was expected to have considerable effect. In Figs. 31 and 32 the data for these rough electrodes are compared with the data for the same electrodes but with smooth surfaces. The data in Fig. 31 suggest that SF_6 is indeed insensitive to the smaller grooves, but in the presence of the deeper grooves the least sensitivity to roughness is achieved with $\sim 5\%$ SF_6 and 95% N_2 . The data in Fig. 32 suggests that a mixture of $\sim 10\%$ $\text{c-C}_4\text{F}_8$ and 90% N_2 is almost entirely insensitive to the lesser degree of roughness, and for the greater roughness a mixture of $\sim 5\%$ $\text{c-C}_4\text{F}_8$ and 95% N_2 is least sensitive. These studies are continuing.

Fig. 27. Breakdown voltages for SF_6/N_2 mixtures with cylindrical electrode radii of 0.75 and 2 cm. Inner electrode has 2 in. long center section with spiral grooves 0.004 in. deep. ($\circ$) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 28. Breakdown voltages for SF_6/N_2 mixtures with cylindrical electrode radii of 0.75 and 2 cm. Inner electrode has 2 in. long center section with spiral grooves 0.020 in. deep. ($\circ$) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 29. Breakdown voltages for $c\text{-C}_4\text{F}_8/\text{N}_2$ mixtures with cylindrical electrode radii of 0.75 and 2 cm. Inner electrode has 2 in. long center section with spiral grooves of 0.004 in. deep. ($\circ$) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 30. Breakdown voltages for $c\text{-C}_4\text{F}_8/\text{N}_2$ mixtures with cylindrical electrode radii of 0.75 and 2 cm. Inner electrode has 2 in. long center section with spiral groove 0.020 in. deep. (o) inner electrode at positive potential, (o) inner electrode at negative potential, (Δ) normalized uniform field data.

Fig. 31. Ratios of breakdown voltages for SF_6/N_2 mixtures with rough (grooved) inner electrodes (V_R) and with smooth electrodes (V_{SM}) of 0.75-cm radius, each with outer cylinder radius of 2 cm (negative polarity).

ORNL-DWG. 78-9090

Fig. 32. Ratios of breakdown voltages for c-C₄F₈/N₂ mixtures with rough (grooved) inner electrodes (V_R) and with smooth electrodes (V_{SM}) of 0.75-cm radius, each with outer cylinder radius of 2 cm.

VIII. IMPULSE STUDIES

A new cage for impulse studies has been erected in a newly acquired laboratory. The new cage has the dimensions 12 ft x 15 ft x 12 ft high. This large shielded volume allows us to conduct impulse and surge studies of dielectric gases. The impulse generator that we have acquired has a maximum peak voltage of 250 kV with 600 J of stored energy.

A picture of the assembled impulse generator-voltage divider and the test chamber is shown in Fig. 33. Tests of the new assembly are in progress.

Fig. 33. Impulse-test apparatus inside shielded cage.
1) 250 kV impulse generator
2) 10,000 : 1 voltage divider for peak voltage reading
3) 10,000 : 1 voltage divider for waveshape analysis
4) test chamber

IX. ENVIRONMENTAL ASPECTS OF DIELECTRIC GASES

In assessing the environmental acceptability of a gas insulating system it is desirable that the dielectric (1) is nontoxic; (2) has nontoxic decomposition products; (3) is stable following repeated breakdowns; and (4) is stable during long periods of electrical stress.

Stability of the dielectric is presently being studied on two fronts. First, time-of-flight mass spectrometry is used to measure initial products by detecting negative ions formed by low-energy electron impact on dielectric gases. Second, final decomposition products are identified by gas chromatography-mass spectrometry combination following the sparking of these dielectric gases.

A. Initial Fragmentation of 2-C₄F₈

Fragmentation of 2-C₄F₈ is extensive, as can be seen in Fig. 34 and Table 5. The ions formed include C₄F₇^{-*}, C₄F₆^{-*}, C₃F₅^{-*}, C₃F₃⁻, C₂F₃⁻, CF₃⁻, and F⁻. The most intense negative ion appearing in the spectrum is the parent ion, C₄F₈^{-*}, formed by electron attachment at ~0.0 eV. It is interesting to note that for this molecule, even thermal energy electrons dissociatively attach to the molecule, resulting in the formation of C₄F₇^{-*} and C₄F₆^{-*}. At energies above ~1 eV, F⁻ is the most abundant ion.

B. Initial Fragmentation of c-C₄F₈

The cyclic isomer of C₄F₈ has also been studied. Its fragmentation pattern, Fig. 35, is significantly different from that of 2-C₄F₈, indicating the importance of the details of molecular structure on the decomposition process. As is shown in Table 5 the integrated F⁻ intensity is

Fig. 34. Negative ions formed by electron impact on 2- C_4F_8 (perfluorobutene-2).

Fig. 35. Negative ions formed by electron impact on c-C₄F₈ (perfluorocyclobutane).

Table 5. Negative ions produced in 2-C₄F₈, c-C₄F₈ and 2-C₄F₆ under electron impact

Negative ion	Positions of negative ion peaks (eV)	% of total ion production ^a
<u>2-C₄F₈ (perfluorobutene-2)</u>		
C ₄ F ₈ ^{-*}	~0.0, 4.1, 7.4	83.4
C ₄ F ₇ ^{-*}	~0.0	1.5
C ₄ F ₆ ^{-*}	~0.0, 0.7	0.4
C ₃ F ₅ ^{-*}	2.3, 4.2	0.9
C ₃ F ₃ ⁻	5.1	0.4
C ₂ F ₃ ⁻	5.4	0.2
CF ₃ ⁻	5.3	0.6
F ⁻	5.2	12.7
<hr/>		
<u>c-C₄F₈ (perfluorocyclobutane)</u>		
C ₄ F ₈ ^{-*}	~0.0	56.3
C ₃ F ₅ ⁻	4.1	0.6
C ₂ F ₃ ⁻	4.9, 7.9	0.4
CF ₃ ⁻	4.8	1.1
F ⁻	4.8, 6.5, 7.9, 10.2	41.6
<hr/>		
<u>2-C₄F₆ (perfluoro-2-butyne)</u>		
C ₄ F ₆ ^{-*}	~0.0	96.3
C ₃ F ₃ ⁻	1.5, 5.0	2.5
CF ₃ ⁻	5.9	1.1
F ⁻	5.3	0.1

^a Ratio of integrated ion intensities to the total ion production in the range covered in this work (typically 0-10 eV).

comparable to the parent ion intensity for the range of electron energy studied. However, no fragmentation is seen at thermal energy. We intend to study the final decomposition products of this dielectric.

C. Initial Fragmentation of 2-C₄F₆

This dielectric has been studied both for its initial products and for its final stable products. Perfluoro-2-butyne exhibits very little fragmentation under direct electron impact (Fig. 36). The only ions formed in addition to the parent ion, C₄F₆^{-*}, are C₃F₃⁻, F⁻, and CF₃⁻. Unlike the C₄F₈ gases, C₃F₃⁻ is the most prominent ion at energies greater than 1 eV for 2-C₄F₆. No fragmentation is seen at ~0.0 eV (Fig. 36).

D. Final Decomposition Products of 2-C₄F₆

Samples of 2-C₄F₆ having been sparked 1000 and 4000 times were passed through a gas chromatograph. The separated components were then identified by their characteristic positive ion mass spectra. Each spark delivered ~5 J of energy to the dielectric. In comparison to a pure sample, the sparked gas was found to contain small amounts of CF₄, C₂F₄, C₂F₆, and C₃F₈ (see Fig. 37).

Solid deposits were also analyzed for carbon (by high temperature oxidation) and for fluorine (by neutron activation) and the content was found to be 55% and 25% (by weight), respectively.

E. Electrical Stress

It is known that low-energy electrons fragment dielectric gases including SF₆. Even without a breakdown, electrons can acquire sufficient

Fig. 36. Negative ions formed by electron impact on 2- C_4F_6 (perfluoro-2-butyne).

ORNL-DWG. 78-8874

Fig. 37. Final decomposition products for 2-C₄F₆ (perfluoro-2-butyne) after 0, 1000, and 4000 sparks as determined by chromatography-mass spectrometry.

energy in the presence of strong fields to disrupt the molecule. Since gaseous insulation will be subjected to electrical stress for periods of months or years, it is highly desirable to analyze stressed gases for decomposition products. Sulfur hexafluoride is presently being studied under these conditions.

F. Toxicity Studies

In response to information that we received from Dr. M. Kegelmann of Dupont on the toxicity of 2-C₄F₆ (perfluoro-2-butyne) we decided to have measurements made by Dr. H. Witschi of the Toxicology Section of the Biology Division of ORNL on the inhalation toxicity of 2-C₄F₆. A check of the Dupont data was considered necessary in light of our experience with the presence of impurities--especially C₄Cl₂F₆ which is a known²³ toxic compound--in the 2-C₄F₆ samples that we received from the manufacturer (Columbia Organic Chemical Co.).

A copy of Dr. Witschi's report on his tests is included as Appendix II to this report. Special care was taken to check the 2-C₄F₆ for impurities before the inhalation study and a cold trap was used to ensure that no impurities were introduced to the test cell. Dr. Witschi's findings agree with the Dupont report that 2-C₄F₆ is highly toxic.

X. APPARATUS

A. High Pressure-High Temperature Apparatus

During this period the high pressure, variable temperature apparatus was put into operation. A series of tests on the cooling system were undertaken to determine the uniformity of the temperature inside the chamber. A digital controller was used to monitor seven thermocouples positioned throughout the chamber. A stable temperature gradient of $\pm 2^{\circ}\text{C}$ was maintained for several hours at -50°C . Good regulation was also possible at higher temperatures in the range from 0 to -50°C . The insulating oven housing was not available at the time of these tests, but we have since received it and are now using it to stabilize further the temperature.

Temperature testing of the high voltage cable provided by Delta Ray Corporation has shown that it melts at $\approx 110^{\circ}\text{C}$. This has limited our measurements to $\approx 90^{\circ}\text{C}$. To insure the high voltage cable never gets above 90°C , a water cooled copper coil was placed around the cable from the point it enters the heating jacket to and including the flange at the test chamber.

Two pieces of high voltage cable were irradiated with γ -rays (the first at 3×10^7 rads over 3 hr and the second at 6×10^7 rads over a period of 6 hr). Both pieces of irradiated cable did not melt at 180°C . We plan to irradiate a section of new cable with γ -rays and install it in this apparatus, thus allowing measurements to be made to at least 150°C .

B. Breakdown Products Apparatus

A small test chamber has been constructed to study breakdown products

of dielectric gases. It has a port for the introduction and removal of gases, a high voltage feedthrough port, a micrometer linear motion feedthrough port to adjust accurately electrode gap spacing and a port containing a sapphire window. High voltage is supplied by a Sorensen 60 kV power supply. The energy of each spark is controlled in a repeatable fashion by discharging in each breakdown a 0.1 μ F capacitor, charged from the power supply through a large resistance. A Hewlett-Packard electronic counter is used to count the number of breakdowns during a given experiment.

C. Modifications on Our Original Breakdown Apparatus

This apparatus is now using a 100 kV Spellman power supply which has been modified to be remotely controlled by our existing control circuits. In order to obtain a more nonuniform field electrode geometry, a 1/8 in. diameter stainless steel sphere has been attached to the top of a 1 1/2 in. diameter sphere as the negative high voltage electrode and a second 1 1/2 in. diameter sphere as a ground electrode to form a sphere on sphere-sphere electrode geometry. Data using this configuration are presented in sections II and VI.

D. Partial Discharge Measurements

A partial discharge detector manufactured by the James G. Biddle Co. has been used with the applied studies facility. This instrument has been used to measure corona inception voltages.

E. New Equipment

We have received the 300 kV DC power supply from the Delta Ray Corporation. It is now being assembled and checked out to be used with existing breakdown apparatus.

A new Tektronix 466 storage oscilloscope has been ordered and received during this reporting period. This oscilloscope has an optional Polaroid compact camera and the capability of operating from a 12 or 24 VDC power source in order to isolate the oscilloscope from regular power line circuits. At the present time, this oscilloscope is being used in setting up and trouble-shooting equipment to be used for impulse studies.

F. Camera

An Imacon 790 image converter camera to be used in our studies of the physical processes occurring at the onset of gas breakdown has been ordered. With this camera we will be able to take 16 frames at up to 20 million frames per second with each frame exposed for 10 nsec. The camera can also be used in a streak mode to study the continuous development of breakdown with a possible time resolution of one nanosecond. The Imacon 790 will provide a versatile addition to our measurement techniques in breakdown studies.

XI. INTERNATIONAL SYMPOSIUM ON GASEOUS DIELECTRICS

In October, 1977, a review of submitted abstracts was conducted and a total of twenty-nine papers, including the invited ones, were selected for presentation at the symposium. Extended abstracts were received in December, 1977, from the contributing authors and full length papers from the invited speakers in January, 1978. Subsequently, extensive editing of all the manuscripts was performed.

The final program and abstracts of the symposium were mailed in January, 1978, to about three hundred selected individuals throughout the world. On March 5-8, the symposium was held with one hundred participants. About one third of the attendees came from eleven countries outside the United States. Stimulating and informative presentations and discussions were held. Much emphasis was placed by the participants on the need for basic data to permit the understanding and improvement of the gas dielectric and its utilization in practice. Interaction among the scientists and engineers of the industrial, applied, and basic areas identified matters of mutual concern that should be investigated further. The presentation made by D.R. James of ORNL and the tour of our laboratories were well received.

In response to a post-conference questionnaire, participants unanimously expressed the desire to continue the symposium in future years at a place and time selected by an international committee formed for that purpose.

Final editing of the symposium proceedings is continuing since the discussions held after each presentation and during the panel sessions were recorded. Copies of the proceedings will be mailed in June, 1978.

XII. VISITS AND CONTACTS

During this period we have been visited by many colleagues who attended the meeting of the Division of Electron and Atomic Physics of the American Physical Society in Knoxville, Tennessee, in November, 1977, and the International Symposium on Gaseous Dielectrics in March, 1978. Among our other visitors are: Professor D. Asmus of the Hahn-Meitner Institute, West Germany; Professor T.W. Hänsch of Stanford University; Professor F. Linder of the University of Kaiserslautern, W. Germany; Professor J.K. Thomas of the University of Notre Dame; Professor J.B. Birks of the University of Manchester, England; Dr. I.C. Walker of Yale University; Dr. R. Crompton of the Australian National University; Dr. M.J. Pilling of Oxford University; Dr. S. Rice of the University of Toronto; Dr. F.D. Osterholtz of Union Carbide Corporation and Mr. J. Gracia of the Department of Energy, Oak Ridge Operations.

Additionally we have had many discussions with colleagues at Oak Ridge National Laboratory, universities, research centers, industrial laboratories, and funding agencies in this country and overseas.

REFERENCES

1. L. G. Christophorou, D. R. James, R. Y. Pai, R. A. Mathis, M. O. Pace, D. W. Bouldin, A. A. Christodoulides, and C. C. Chan, *High Voltage Research (Breakdown Strengths of Gaseous and Liquid Insulators)* ORNL/TM-6113 (November 1977).
2. L. G. Christophorou, "Elementary Electron-Molecule Interactions and Negative Ion Resonances at Subexcitation Energies and Their Significance in Gaseous Dielectrics," *Proceedings of the XIIIth International Conference on Phenomena in Ionized Gases, Berlin, GDR, Sept. 11-17, 1977*, Vol. II (1978).
3. D. R. James, L. G. Christophorou, R. Y. Pai, M. O. Pace, R. A. Mathis, I. Sauers, and C. C. Chan, "Dielectric Strengths of New Gases and Gas Mixtures," *Proceedings of the International Symposium on Gaseous Dielectrics, Knoxville, Tennessee, Mar. 6-8, 1978*, CONF-780301 (1978; in press).
4. M. O. Pace, L. G. Christophorou, D. R. James, R. Y. Pai, R. A. Mathis, and D. W. Bouldin, "Improved Unitary and Multicomponent Gaseous Insulators," *IEEE Trans. Elect. Insul.* Vol. EI-13, 31 (1978).
5. L. G. Christophorou, D. R. James, R. Y. Pai, M. O. Pace, R. A. Mathis, and D. W. Bouldin, *High Voltage Research (Breakdown Strengths of Gaseous and Liquid Insulators)*, ORNL/TM-5604 (September 1976).
6. L. G. Christophorou, D. R. James, R. Y. Pai, M. O. Pace, R. A. Mathis, and D. W. Bouldin, *High Voltage Research (Breakdown Strengths of Gaseous and Liquid Insulators)*, ORNL/TM-5917 (June 1977).
7. L. G. Christophorou, *Atomic and Molecular Radiation Physics*, Wiley-Interscience, New York, 1971.

8. D. E. Donohue, J. A. Schiavone, and R. S. Freund, *J. Chem. Phys.* 67, 769 (1977).
9. J. A. Beran and L. Kevan, *J. Phys. Chem.* 73, 3866 (1969).
10. F. W. Lampe, J. L. Franklin, and F. H. Field, *J. Am. Chem. Soc.* 79, 6129 (1957).
11. D. Rapp and P. Englander-Golden, *J. Chem. Phys.* 43, 1464 (1965).
12. H. H. Landolt and R. Börnstein, *Tables of Chemical Data, Zahlenwerte und Funktionen*, pp. 510-513, Vol. 1, Part 3, Springer, Berlin, 1951.
13. J. A. Beran and L. Kevan, *J. Phys. Chem.* 73, 3860 (1969).
14. R.J.W. LeFevre, *Adv. Phys. Org. Chem.* 3, 1 (1966).
15. G. J. Moody and J.D.R. Thomas, *Dipole Moments in Inorganic Chemistry*, p. 21, Edward Arnold Publishers, Ltd., London, 1971.
16. H. M. Rosenstock, K. Draxl, B. W. Steiner, and J. T. Herron, *Energetics of Gaseous Ions*, *J. Phys. Chem. Ref. Data* 6, 1977 (Supplement No. 1).
17. D. E. Golden, *Phys. Rev. Lett.* 17, 847 (1966).
18. A. G. Engelhardt, A. V. Phelps and C.G. Risk, *Westinghouse Research Laboratory Scientific Paper*, 64-928-113-P4 (1964).
19. S. K. Srivastava, S. Trajmar, A. Chutjian and W. Williams, *J. Chem. Phys.* 64, 2767 (1967).
20. K. Rohr, *J. Phys. B: Atom. Molec. Phys.* 10, 1175 (1977).
21. D. E. Golden and H. W. Bandel, *Phys. Rev.* 149, 58 (1966).
22. H.S.W. Massey and E.H.S. Burhop, *Electronic and Ionic Impact Phenomena: Vol. 1, Collisions of Electrons with Atoms*, p. 26, Oxford University Press, (1969).
23. E. N. Cohen, H. W. Brewer, J. W. Bellville, and R. Sher, *Anesthesiology* 26, 140 (1965).

APPENDIX I

Abstracts of Papers Presented at
the Washington, D.C. Meeting of the
American Physical Society
April 24-27, 1978

Electron Attachment to Perfluorocarbon Compounds.

I.* A. A. CHRISTODOULIDES, L. G. CHRISTOPHOROU, R. Y. PAI, and C. M. TUNG, Oak Ridge Nat'l Lab.—Electron attachment rates as a function of the pressure-reduced electric field, E/P_{298} , have been measured for trace amounts ($<10^{-3}$ torr) each of 2- C_4F_6 (hexafluoro-2-butyne), 1,3- C_4F_6 (hexafluoro-1,3-butadiene), c- C_4F_6 (hexafluorocyclobutene), 2- C_4F_8 (octafluoro-2-butene), and c- C_4F_8 (octafluorocyclobutane) in mixtures with N_2 or Ar (pressures 500–2000 torr). The thermal attachment rates for these molecules were found to be 1.6×10^9 , 3.6×10^9 , 4.0×10^9 , 1.4×10^9 , and $0.4 \times 10^9 \text{ sec}^{-1} \text{ torr}^{-1}$, respectively. From the attachment-rate data, the attachment cross sections, $\sigma_a(\epsilon)$, as a function of electron energy, ϵ , have been determined using the swarm-unfolding technique.¹ For all five molecules, $\sigma_a(\epsilon)$ are large, and except for c- C_4F_6 , they show a maximum at ~ 0.2 eV and another in the range ~ 0.5 to ~ 1.1 eV. For c- C_4F_6 , only a shoulder around 0.2 eV was observed. Although the positions of the maxima in $\sigma_a(\epsilon)$ vary only slightly among these compounds, the magnitude and energy dependence of $\sigma_a(\epsilon)$ depend strongly on structure.

*Research sponsored by DOE under contract with UCCND.

¹L. G. Christophorou, D. L. McCorkle, and V. E. Anderson, J. Phys. B 4, 1163 (1971).

Electron Attachment to Perfluorocarbon Compounds.

II.* R. Y. PAI, L. G. CHRISTOPHOROU, and A. A. CHRISTODOULIDES, Oak Ridge Nat'l Lab.—Electron attachment rates as a function of mean electron energy, and electron attachment cross sections, $\sigma_a(\epsilon)$, as a function of electron energy, ϵ , have been determined for $c\text{-C}_5\text{F}_8$ (octafluorocyclopentene); $c\text{-C}_6\text{F}_{10}$ (decafluorocyclohexene), C_6F_{12} (perfluorodimethylcyclobutane), C_7F_8 (octafluorotoluene), and C_8F_{16} (perfluoro-1,3-dimethylcyclohexane). The thermal (298°K) attachment rates for these molecules are 11×10^9 , 11.2×10^9 , 4.5×10^9 , 7.9×10^9 , and $2.4 \times 10^9 \text{ sec}^{-1} \text{ torr}^{-1}$, respectively. Their $\sigma_a(\epsilon)$ are largest at thermal energies. The $\sigma_a(\epsilon)$ for $c\text{-C}_5\text{F}_8$, $c\text{-C}_6\text{F}_{10}$, and C_8F_{16} exhibit maxima at 0.27, 0.25, and 0.16 eV, respectively; the $\sigma_a(\epsilon)$ of C_6F_{12} shows a shoulder at ~ 0.15 eV. Another broad maximum at higher energies (~ 0.8 to ~ 1.2 eV) was observed for $c\text{-C}_5\text{F}_8$, $c\text{-C}_6\text{F}_{10}$, and C_7F_8 . With the exception of $c\text{-C}_4\text{F}_8$, $\sigma_a(\epsilon)$ for all the perfluorocarbons studied (I and II) are very large ($\sim 3 \times 10^{-15} \text{ cm}^2$) below ~ 0.1 eV and, except for $c\text{-C}_4\text{F}_6$, they are still large ($\sim 10^{-16} \text{ cm}^2$) to ~ 1.0 eV. The significance of this to the performance of these compounds as gaseous dielectrics and as additives to gaseous dielectric mixtures¹ will be discussed.

*Research sponsored by DOE under contract with UCCND.

¹L.G. Christophorou et al., ORNL/TM-6113 (1977).

APPENDIX II

INTRA-LABORATORY CORRESPONDENCE

OAK RIDGE NATIONAL LABORATORY

April 4, 1978

TO: Dr. L. G. Christophorou
Health and Safety Research Division

FROM: Hanspeter Witschi

RE: Acute inhalation toxicity of Perfluoro-2-butyne
(PFBY-2) in mice

On March 31, 1978, we examined acute inhalation toxicity of PFBY-2 in mice. Ten male mice, average 20 g and 6 weeks old, were placed into a plexiglass inhalation chamber, volume approximately 40 l. The chamber was ventilated with compressed air at a flow rate of 10 l/min. Into the air stream was metered the PFBY-2 at a nominal flow rate of 10 ml/min. This flow rate was determined by water displacement at the beginning of the experiment and assumed to remain constant. The theoretical PFBY-2 concentration in the chamber was thus 1000 ppm and equilibration time to reach 990 ppm 18-20 min.

The animals showed signs of respiratory irritation within 30 min after being introduced into the chamber; they became agitated and repeatedly wiped their snouts. Later, the breathing became visibly labored. After 2.5 hr, 8 out of 10 animals had died and the remaining two died at 3 hours. The lungs were inspected in a few animals and found to be heavy, oedematous hemorrhagic, with froth and fluid in the airways.

PFBY-2, at a concentration of 1000 ppm thus kills mice in less than 3 hours. The signs of acute toxicity are similar to the ones described for rats.

HPW/jms

APPENDIX III

DIELECTRIC STRENGTHS OF NEW GASES AND GAS MIXTURES*

D. R. James, L. G. Christophorou,[†] R. Y. Pai, M. O. Pace,[†]
R. A. Mathis, I. Sauers, and C. C. Chan
Health and Safety Research Division, Oak Ridge National Laboratory,
Oak Ridge, Tennessee 37830

ABSTRACT

We have argued earlier and we emphasize further in this paper that the most effective gaseous dielectrics are gas mixtures with components chosen on the basis of fundamental physicochemical knowledge, especially on low-energy electron-molecule interactions. On the basis of such knowledge, especially on electron attachment and electron slowing down, a number of new gases and gas mixtures have been found with breakdown strengths superior to pure SF₆. These include the unitary gases c-C₄F₈ (perfluorocyclobutane), C₄F₈ (perfluorobutene-2), C₄F₆ (perfluoro-2-butyne), C₆F₁₀ (perfluorocyclohexene), C₅F₈ (perfluorocyclopentene), and C₆F₁₂ (perfluorodimethylcyclobutane), and the multi-component gas mixtures 20% C₄F₆ + 80% SF₆, 40% C₄F₆ + 60% N₂, 50% C₄F₆ + 50% SF₆, and 30% C₄F₆ + 20% SF₆ + 50% N₂ with DC breakdown strengths relative to SF₆ of 1 equal to 1.4, 1.8, 2.2, 2.1, 2.2, 2.4, 1.3, 1.4, 1.75, and 1.33, respectively. Our findings on these and other systems will be presented and discussed. Results will be presented and discussed, also, on the dielectric strengths of some of the above new gases measured with cylindrical electrode geometries using different center conductor diameters. Finally, our findings on the initial decomposition products of some of the new insulators caused by electron impact will be presented and their implications assessed.

INTRODUCTION

As electric transmission line voltage levels continue to increase, there is a corresponding need to upgrade the performance of gaseous dielectrics. Existing gaseous insulators clearly do not meet all of

*Research sponsored by the Department of Energy under contract with Union Carbide Corporation.

[†]Also, The University of Tennessee, Knoxville, Tennessee 37916.

the requirements of the power industry, and it is unlikely that any single gas will be satisfactory for all conditions. Solutions, therefore, to the many and varied problems and needs relating to high voltage insulation (and improvements over present procedures) must be sought in the development and use of multicomponent gas mixtures.

We anticipate that the best multicomponent gaseous insulators will be comprised of components selected according to basic knowledge on their physical and chemical properties. Especially significant among these are the basic processes involved in the interaction of low-energy electrons with the dielectric gas molecules, such as electron attachment, electron energy loss, and electron impact ionization, as a function of electron energy and the relation of these to molecular structure.

We have undertaken a systematic investigation of the basic and applied aspects of the dielectric strengths of unitary and multicomponent gaseous systems, and in this paper we present and briefly discuss some of the pertinent findings of this work.

APPARATUS

Two pieces of apparatus have been employed in the present investigations of breakdown voltages of gases and gas mixtures. The first apparatus consisted of a small stainless steel chamber approximately 6 liters in volume which could be evacuated to less than 10^{-6} torr. The high voltage electrode was a 3/4-in. stainless steel sphere and the ground electrode was a 3-1/2-in. stainless steel plane mounted onto a micrometer drive. Negative high voltage was applied to the sphere by a 60-kV power supply. The electrode separation was kept small to approximate uniform field conditions (e.g., a 1-mm electrode gap resulted in a field nonuniformity of $\sim 3.5\%$).

The second apparatus comprised a larger chamber of ~ 40 liters volume which was routinely evacuated to less than 10^{-6} torr before gas was admitted to the chamber. The electrode assembly consisted of two stainless steel planes, the profiles of which were designed according to the work of Pearson and Harrison.¹ A 300-kV DC power supply (Deltatron L300-2C) from Delta Ray Corporation provided a negative high voltage relative to the grounded electrode.

Both apparatuses had similar controllers which automatically ramped the voltage, detected the spark, and held the breakdown voltage reading on a digital voltmeter. Ultraviolet light from a deuterium lamp was used to irradiate the electrodes. To obtain a data point, usually a minimum of ten breakdowns were recorded at each value of P and d (P is the gas pressure and d is the electrode separation), and the average value and standard deviation were calculated. The ratio of the standard deviation to the mean was used as a measure of the scatter in the data. In general this scatter was $\sim 2\%$ for the sphere-plane geometry, although at the highest values of Pd employed, this scatter was at times larger (still, however, $< 5\%$). With the plane-plane electrode geometry the scatter was $\sim 1\%$ below 200 kV and typically between 2 to 3% above ~ 200 kV.

BREAKDOWN STRENGTHS - UNITARY GASES

Dielectric Gases with Vapor Pressures in Excess of One Atmosphere

In our investigations we have found a number of high vapor pressure (> 1 atm at ambient temperature) gases which have high dielectric strengths. Some of these gases, their dielectric strengths relative to that of SF_6 , and their vapor pressures at ambient temperatures are listed in Table 1. In Fig. 1 are shown the breakdown voltages, V_s , for a number of unitary gases as functions of Pd . The fluorocarbons were found to have the highest dielectric strength; C_4F_6 (perfluoro-2-butyne) in particular has more than twice the dielectric strength of SF_6 . The double-bonded C_4F_8 (perfluorocyclobutene-2) and the cyclic- C_4F_8 (perfluorocyclobutane) compounds are two other fluorocarbons with high dielectric strengths. Perfluoropropane (C_3F_8), although with eight fluorine atoms, has a dielectric strength slightly lower than SF_6 . This molecule, however, has no double bonds and attaches low-energy electrons very weakly.³

The breakdown voltage, V_s , in uniform electric fields was found to be a function of Pd and not an explicit function of P alone. A possible exception, however, seems to be SF_6 which for pressures > 2000 torr shows⁴ deviation from Paschen's law.

Table 1. Relative DC Breakdown Strengths of
Some Unitary Gases (Vapor Pressures ≥ 1 Atm)^a

Gas	Relative Strength	Vapor Pressure Atm ($^{\circ}$ C)
C ₄ F ₆ (perfluoro-2-butyne)	2.2	$\geq 4.8^b$ (23)
C ₄ F ₈ (perfluorobutene-2)	1.7-1.8	2.02 ^c (21.1)
c-C ₄ F ₆ (perfluorocyclobutene)	1.7	$> 1^d$
C ₄ F ₆ (perfluoro-1,3-butadiene)	1.4	$> 1^e$
c-C ₄ F ₈ (perfluorocyclobutane)	1.3-1.4	2.9 ^f (24.3)
SF ₆ (sulfur hexafluoride)	1.0	22.77 ^c (21.1)
C ₃ F ₈ (perfluoropropane)	0.93	7.81 ^c (21.1)
N ₂ (nitrogen)	0.40	g
CO ₂ (carbon dioxide)	0.37	57.5 ^c (21.1)

^aAll breakdown strength data are from Ref. 4 except those on c-C₄F₆ which are unpublished recent results by the Oak Ridge group.

^bPresent estimated value.

^cWilliam Braker and Allen L. Mossman, Matheson Gas Data Book, 5th Ed., Matheson Gas Products, East Rutherford, New Jersey, 1971.

^dBoiling point = 7.4-7.6 $^{\circ}$ C.

^eBoiling point = 5-6 $^{\circ}$ C.

^fE. C. Coyner and D. Hanesian, Freon Technical Bulletin EL-5, E. I. du Pont de Nemours and Company, Inc., 1964.

^gCritical temperature -147.1 $^{\circ}$ C; N₂ cannot be liquefied at temperatures higher than this.

Fig. 1. Breakdown voltage, V_S , as a function of P_d for high pressure (~ 1 atm) unitary gases. The CO_2 data are from Ref. 2.

Dielectric Gases with Vapor Pressures Less Than One Atmosphere

Many compounds with vapor pressures less than one atmosphere at room temperature were found to have higher dielectric strengths than SF_6 at comparable pressures. The relative breakdown strengths of some of these are given in Table 2, and the V_S vs P_d curves are shown in Fig. 2. The pressures employed ranged from 20 torr for C_7F_8 (octafluorotoluene) to 281 torr for C_4F_6 (hexafluoro-1,3-butadiene). Comparisons with SF_6 were made only when SF_6 could be measured at the same or nearly the same pressure. The curvature of the breakdown voltage vs P_d seen in Fig. 2 is due to the low pressures employed which required the electrode

Table 2. Relative DC Breakdown Strengths of
Some Low Vapor Pressure Compounds^a

Compound	Relative Strength
C ₆ F ₁₂ (mixture of 1,2- and 1,3-perfluorodimethylcyclobutane) ^b	2.3-2.4
C ₅ F ₈ (perfluorocyclopentene) ^c	2.1-2.2
C ₆ F ₁₀ (perfluorocyclohexene)	1.9-2.2
C ₇ F ₁₄ (perfluoromethylcyclohexane) ^d	2.1
C ₈ F ₁₆ (perfluoro-1,3-dimethylcyclohexane)	~2.3 ^e
C ₇ F ₈ (octafluorotoluene)	~2 ^f
C ₇ F ₁₄ (perfluoroheptene-1)	1.2
SF ₆ (sulfur hexafluoride)	1.0

^aData from Ref. 4 except as noted.

^bAt 26.7°C the vapor pressure is 394.3 torr.

^cBoiling point = 25°C.

^dAt 21.7°C the vapor pressure is ~95 torr.

^eAt low pressures the V_s for this compound was found to be 1.3 times that of C₄F₆ under identical experimental conditions.

^fUnpublished result of the Oak Ridge group, measured with respect to C₈F₁₆ under identical experimental conditions.

separation to be relatively large (up to 10 mm in some cases) in order to obtain Pd values in the range $0.5 \lesssim Pd \lesssim 2.5$ atm-mm. Hence, the electric field was highly nonuniform in these cases, and in general the breakdown voltage was not a linear function of Pd.

These low vapor pressure compounds, although unsuitable by themselves as dielectrics due to their low vapor pressures at room temperature, may

Fig. 2. Breakdown voltage, V_s , as a function of Pd for low pressure (<1 atm) unitary gases at the indicated pressures for sphere-plane electrode geometry.

have potential use as additives to higher pressure buffer gases such as N_2 . For example, a 10% C_6F_{10} /90% N_2 mixture at 500 torr total pressure has a 20% higher breakdown voltage than a 10% SF_6 /90% N_2 mixture at the same pressure. But, even more importantly, the study of these gases provides basic information necessary for the understanding of the role of fundamental physical processes in the electrical breakdown.

The Role of Electron Attachment as a Function of Electron Energy

In order to develop new improved gas dielectrics, the basic physical properties of the dielectric itself must be identified and understood, especially in relation to their effect on the breakdown voltage. We have been investigating the role of one such basic property of the dielectric; namely, electron attachment as a function of electron energy. Although our systematic study of the electron attachment properties of the compounds in Tables 1 and 2 is still not complete, the data presented in Fig. 3 are quite revealing.

Let us, then, draw our attention to Fig. 3 where the electron attachment cross section as a function of electron energy, $\sigma_a(\epsilon)$, is plotted for several gases of high dielectric strength.⁴⁻⁶ The line designated as $\pi\lambda^2$ represents the maximum s-wave capture cross section ($\lambda = \lambda/2\pi$ and λ is the electron deBroglie wavelength). The $\sigma_a(\epsilon)$ for SF_6 approaches the theoretical maximum at near-thermal energies and is quite large at ~ 0.3 eV. (The peak at ~ 0.3 eV is due to SF_5^- while at thermal energies SF_6^- is the dominant ion formed.) At energies $\gtrsim 0.4$ eV, the SF_6 capture cross section rapidly decreases so that SF_6 cannot effectively capture electrons with kinetic energies in excess of this energy. It is seen from Fig. 3 that the attachment cross sections for $c-C_4F_8$, C_4F_8 , and C_4F_6 remain substantial to electron energies $\gtrsim 1$ eV. These latter gases, therefore, are capable of capturing effectively electrons to much higher energies than SF_6 . Our breakdown measurements (Table 1) clearly show that for the latter group of compounds the breakdown strengths are significantly higher than that of SF_6 . On the basis of these findings and additional measurements currently in progress,⁶

Fig. 3. Electron attachment cross sections as a function of electron energy for SF6, c-C4F8, C4F8 (perfluorobutene-2), and C4F6 (perfluoro-2-butyne). $\pi\lambda^2$ is the maximum s-wave electron capture cross section (Refs. 5 and 6).

the efficient capture of electrons in the range of energies $0.4 \leq \epsilon \leq 1.2$ eV evidently reduces significantly the number of free electrons available for initiating breakdown, with a resultant increase in the breakdown strength of the dielectric. More generally, the overlap of the electron energy (or velocity) distribution with the electron attachment cross section must be sufficiently large to cause a substantial increase in the breakdown voltage.

Optimizing the Gaseous Dielectric

We have suggested earlier⁵ the criteria for an optimum gas dielectric; namely, that a good dielectric should maximize the quantity

$$\int_0^{\infty} \sigma_a(\epsilon) f(\epsilon, E/P) d\epsilon \quad [\text{maximize}] \quad (1)$$

and minimize the quantity

$$\int_I^{\infty} \sigma_i(\epsilon) f(\epsilon, E/P) d\epsilon \quad [\text{minimize}], \quad (2)$$

where $\sigma_a(\epsilon)$ and $\sigma_i(\epsilon)$ are the electron-attachment and electron-impact ionization cross sections, respectively, and $f(\epsilon, E/P)$ is the electron energy distribution function as a function of electron energy ϵ and pressure reduced electric field E/P , and I is the ionization threshold energy.

Condition (1) is satisfied when $\sigma_a(\epsilon)$ is as large as possible over as wide an energy range as possible. Since electron attachment processes are resonant processes with cross sections decreasing with increasing energy position of the resonance (see Fig. 3 and Ref. 5), $f(\epsilon, E/P)$ should be shifted to as low an energy as possible. To fulfill condition (2), the ionization threshold would need to be high and the energy distribution shifted to low energies. Thus in each case the electron energies should be reduced as much as possible. Such a reduction in the electron energy is accomplished by elastic and especially

inelastic electron scattering processes, some of which are discussed in the next section on dielectric mixtures.

Important as the electron energy distribution function is in assessing the role of the various basic processes on breakdown [see relations (1) and (2)], to our knowledge presently there are no direct measurements of this quantity for gaseous media under prebreakdown conditions. There exists only a limited indirect knowledge of $f(\epsilon, E/P)$ for some simple gases. The main difficulty in computing $f(\epsilon, E/P)$ from electron transport data lies in the fact that a large amount of basic detailed information on the microscopic cross sections is required, which for a complex molecular gas or a gas mixture makes the indirect deduction of $f(\epsilon, E/P)$ very uncertain. Plans to measure directly $f(\epsilon, E/P)$ for pure polyatomic gases and gas mixtures under prebreakdown conditions are under consideration at our laboratory.

Prior to closing this section, it is emphasized that important as the process of electron attachment is in affecting the dielectric strength of a gaseous medium, it is not the only gas property which determines the behavior of the gaseous dielectric. Elastic and inelastic (especially indirect via negative ion resonances⁵) electron scattering as well as electron impact ionization at low energies can also be crucial [see relations (1) and (2)]. It can be seen, for example, from Fig. 3 that the electron attachment cross section above thermal energies for $c\text{-C}_4\text{F}_8$ is generally higher than that for C_4F_8 (perfluorobutene-2), although the breakdown voltage of $c\text{-C}_4\text{F}_8$ is substantially less than that of its isomer. This may be due to the presence of the double bond in perfluorobutene-2, since, as we have shown earlier for a number of hydrocarbons,³ the presence of double and triple bonds lowers the average electron energy at a given E/P .

Basic studies at our laboratory have been and are being aimed at the identification of the mechanisms of electron energy loss and on the dependence of the cross sections of these on the details of the molecular structure. It is on the basis of such knowledge that we would hope to optimize our choice of dielectric gases.

BREAKDOWN STRENGTHS - GAS MIXTURES

Gas mixtures as dielectrics have the advantage that they can be tailored to a specific need, whereas a unitary gas must be universally good under all conditions. For example, SF_6 performs well in uniform fields, but in the presence of nonuniform fields (as in the case of particle contamination) its strength deteriorates considerably. It is quite possible that gas mixtures can have a greatly improved nonuniform field performance.

There are several ways to approach systematically the development of dielectric gas mixtures, all of which require detailed knowledge of basic cross sections in order to assess the compatibility of the component gases and to maximize synergistic effects. One approach involves the use of several electron attaching gases in combination to map as wide an energy range as possible with large electron attachment cross sections. In this manner, one attempts to approach the theoretical maximum electron attachment cross section (see Fig. 3) and hence maximize expression (1). As far as electron attachment is concerned, this would be the optimal dielectric. Another approach involves the use of efficient electron attaching and electron slowing down gases, the latter being used for the purpose of shifting $f(\epsilon, E/P)$ to lower energy and in such a way as to optimize (1) and (2).

Binary Mixtures of Efficient Electron Attaching Gases

In Table 3 data are presented on the relative breakdown strengths of binary mixtures of C_4F_6 and SF_6 . The relative breakdown strength of the binary mixture increases with the amount of C_4F_6 . The measured relative strengths were in each case larger than the weighted average (fraction of C_4F_6 x relative strength of C_4F_6 + fraction of SF_6 x relative strength of SF_6) calculated by using a relative breakdown strength of 2.2 for C_4F_6 . These results indicate a synergistic effect between the two gases.

Table 3. Relative Breakdown Strengths of Binary Mixtures of
 SF_6 and C_4F_6 (perfluoro-2-butyne)
 (T = 298°K, P_{total} = 500 torr)

Percentage of Mixture		Measured Relative Breakdown Strength	Weighted Average ^a
C_4F_6	SF_6		
5	95	1.10	1.06
10	90	1.17	1.12
20	80	1.30	1.24
50	50	1.75	1.60
0	100	1.00	1.00

^aSee text.

From the discussion given earlier in this section, synergism in the dielectric behavior of a gas mixture must be traced to the details of the interaction of free electrons with the gas molecules comprising the mixture and the magnitudes and energy dependences of the associated cross sections. If the component gases interact with electrons in different energy ranges and with large cross sections, then—depending on the magnitude and energy dependence of their cross sections—they may cooperate in ameliorating the effects of free electrons, especially if the cross sections of each are small outside of a narrow energy range. Sulfur hexafluoride (SF_6) with an attachment cross section $\sigma_a(\epsilon)$ confined mostly to thermal energies would be expected to show a great degree of synergism as an additive with other gases. This is borne out by the data in Tables 3 and 4.

Figure 4 shows the breakdown voltage of a 20% C_4F_6 /80% SF_6 mixture at a high (4.7 atm) total pressure. The relative improvement over pure SF_6 is the same as for the low pressure mixture in Table 3.

Fig. 4. Breakdown voltage, V_s , for pure SF_6 and for $\text{SF}_6/\text{C}_4\text{F}_6$ (perfluoro-2-butyne) and $\text{SF}_6/\text{C}_4\text{F}_6/\text{N}_2$ mixtures as a function of Pd for pressures 3000 to 3500 torr (sphere-sphere electrode geometry).

Binary Mixtures of Efficient Electron Attaching and Electron Slowing Down Gases

Although basic physicochemical knowledge does not yet permit a quantitative prediction of the breakdown strength and other dielectric properties of a gas, the available basic knowledge can be used as a guide for a systematic study of mixtures. An investigation of the breakdown voltages for several electron attaching gas mixtures using N_2 as the electron slowing down agent or buffer gas was made, and the results appear in Fig. 5. The Pd value was held constant at 4.6 atm-mm. By

Fig. 5. Breakdown voltages, V_S , vs percent of electron attaching additive to N_2 by volume (plane-plane electrode geometry).

measuring the breakdown voltage as a function of the percentage of the electron attaching gas, we can compare the synergistic effect of each in combination with N_2 .

For all five gases (SF_6 , C_4F_6 , C_3F_8 , C_4F_8 , and $c-C_4F_8$) the corresponding binary mixtures with N_2 show synergism. As expected from the electron attachment cross sections (Fig. 3), the mixtures with SF_6

show the largest synergism. A mixture of 40% SF_6 /60% N_2 realizes 80% of the dielectric strength of pure SF_6 . The rest of the electron attaching gases show a sharp increase in V_s at low percentage mixtures, but subsequently V_s increases essentially linearly with concentration showing no evidence of the saturation effect evident in the SF_6/N_2 mixtures.

Carbon dioxide (CO_2) also exhibits synergism when combined with electron attaching gases. In Table 4, the breakdown voltage is shown for mixtures of 20% of an efficient electron attaching gas and 80% CO_2 , or 40% CO_2 + 40% N_2 , or 80% N_2 . It is clearly seen that CO_2 is slightly better than N_2 as a buffer gas for $\text{c-C}_4\text{F}_8$. A slight synergism between CO_2 and N_2 is also discernable for the C_4F_8 containing mixtures. These synergistic effects must relate to the electron slowing down properties of CO_2 .^{5,7}

Synergism in Multicomponent Gas Mixtures

Cooperative effects arising from proper combinations of electron attaching and electron slowing down gases can be seen from the data in Table 5, where the dielectric strengths of mixtures (see Ref. 4 for a complete list of these) comprising the gases N_2 , SF_6 , C_4F_6 , and C_3F_8 are listed. Two of the salient features of these data are: (1) C_4F_6 , as is expected from its dielectric strength in the pure form, is very effective as an additive. Thus entries 11 and 12 with the highest percentage of C_4F_6 have the highest breakdown voltage. (2) C_3F_8 by itself or in mixtures with only N_2 (entries 2 and 6) is not particularly effective. When, however, C_3F_8 is used in combination with N_2 , C_4F_6 , and SF_6 —as in entries 9 and 10, 11 and 12, and 13 and 14—it is more effective than an equal amount of SF_6 .

Effect of Indirect Electron Scattering Via Negative Ion Resonances on the Dielectric Strength of Binary Mixtures

The significance of negative ion resonances (NIRs) in slowing down subionization and especially subexcitation electrons has been discussed earlier.⁵ A number of studies have shown that for many substances (see,

Table 4. Mixtures of Effective Electron
Attaching Gases with CO₂
(T = 298°K, P $\approx$ 0.66 atm, Pd = 4.6 atm-mm)

Mixture	Breakdown Voltage ^{a,b} (kV)	Weighted Average (kV)
20% c-C ₄ F ₈ /80% N ₂	25.0	23.1
20% c-C ₄ F ₈ /40% CO ₂ /40% N ₂	25.7	22.2
20% c-C ₄ F ₈ /80% CO ₂	26.0	21.3
20% C ₄ F ₈ /80% N ₂	28.7	26.3
20% C ₄ F ₈ /40% CO ₂ /40% N ₂	28.9	25.4
20% C ₄ F ₈ /80% CO ₂	28.5	24.5
20% C ₄ F ₆ /80% N ₂	40.1	31.3
20% C ₄ F ₆ /40% CO ₂ /40% N ₂	39.1	30.4
20% C ₄ F ₆ /80% CO ₂	38.1	29.5
20% C ₃ F ₈ /80% N ₂	22.8	20.1
20% C ₃ F ₈ /40% CO ₂ /40% N ₂	22.4	19.2
20% C ₃ F ₈ /80% CO ₂	20.8	18.3
20% SF ₆ /80% N ₂	30.1	20.7
20% SF ₆ /40% CO ₂ /40% N ₂	28.7	19.8

^aThe uncertainty is less than 0.1 kV.

^bThese breakdown voltages are averages of ten breakdown measurements taken with plane-plane electrode geometry and 0.275-in. electrode gap.

for example, Refs. 8 and 9) electron scattering (elastic and inelastic) at low energies proceeds predominantly through such states. These electron-molecule (negative ion) states are formed^{7,8,10} when slow electrons interact with molecules and are nonstationary (i.e., they decay, often

Table 5. Dielectric Strengths of Unitary, Binary, and Multicomponent Mixtures of N_2 , SF_6 , C_4F_6 , and C_3F_8
($T = 298^\circ K$, $P \sim 0.66 \text{ atm}$)^a

Percent Component					$V_s \text{ (kV)}$
No.	N_2	SF_6	C_4F_6	C_3F_8	
1	—	100	—	—	40.4
2	—	—	100	—	93.5
3	—	—	—	100	36.4
4	80	20	—	—	30.1
5	80	—	20	—	40.1
6	80	—	—	20	22.8
7	80	10	10	—	36.0
8	80	10	—	10	29.8
9	60	20	20	—	43.2
10	60	10	20	10	47.7
11	50	20	30	—	53.7
12	50	10	30	10	55.4
13	50	20	20	10	47.0
14	50	10	20	20	48.3

^aAverage of ten independent measurements at a Pd value of 4.6 atm-mm (plane-plane electrode geometry).

in as short a time as $\sim 10^{-16}$ sec). Upon decay, the neutral molecule can retain part or all of the impacting electron's energy, the electron being slowed down in the process.

We have investigated the use of systems possessing such NIRs as "electron slowing down" gases in mixtures with one or more highly

electron attaching gases. The electron slowing down gases we used do not normally attach electrons themselves but act to lower the energy of the free electrons so that the electron attaching additive(s) can efficiently remove them in the form of negative ions.

Figure 6 shows the cross sections for vibrational excitation via NIR for CO, N₂, and H₂ as a function of electron energy. These gases were used since basic data for them already exist. Additional basic data are needed. For CO and N₂ the cross sections are the sums of the first eight vibrational levels¹¹; for H₂ the cross section for only the first vibrational level is given since the higher ones are very much lower in magnitude. The H₂ cross section has been multiplied by 1.4 to correct for anisotropic scattering.⁷ The magnitude of the cross sections decrease in the order CO > N₂ > H₂. One would expect on the basis of the NIR cross section data alone that the breakdown voltage should decrease in the order CO > N₂ > H₂. This is clearly seen from the uniform-field measurements on V_s presented in Table 6. V_s decreases in the order CO > N₂ > H₂. Since the electron attachment cross sections for these systems are exceedingly small or zero,⁷ the differences in their dielectric strength is attributed to their relative effectiveness in slowing down electrons via their respective NIRs. Similar conclusions can be drawn from the results on binary mixtures of C₄F₆ and SF₆ each with H₂, N₂, and CO presented in Table 6.

BREAKDOWN STRENGTHS OF GASES/MIXTURES WITH CYLINDRICAL ELECTRODES

In Fig. 7 a and b, preliminary data⁴ are presented on the breakdown voltages of mixtures of SF₆ and c-C₄F₈ each with N₂ obtained using cylindrical electrodes comprising an inner stainless steel electrode of 0.4 cm radius inside an outer cylinder of inner radius of 2 cm. The total pressure was 760 torr (1 atm), and the SF₆/N₂ and c-C₄F₈/N₂ concentration fraction was varied from 0 to 100% by pressure. The outer cylinder was at ground potential, and the inner cylinder was at either polarity of high voltage. Each data point is the average of at least ten breakdowns and for each the random scatter (standard deviation ÷ mean) was less than 3%. The uniform field breakdown strength data shown in

Fig. 6. Electron attachment cross sections, σ_a , as a function of electron energy, ϵ , for the three electron attaching gases, SF_6 , C_4F_6 , and C_6F_{10} , and vibrational excitation cross sections via negative ion resonances for CO , N_2 , and H_2 (see text and Ref. 7).

Fig. 5 for SF_6/N_2 and $\text{c-C}_4\text{F}_8/\text{N}_2$ mixtures have been normalized to the nonuniform field value of the V_s for pure N_2 . Although the normalized uniform and nonuniform field data are not dramatically different, it is interesting to see that the dependence of V_s on the amount of SF_6 in N_2 shows a stronger "saturation" effect in uniform than in nonuniform fields. In the uniform field case, the SF_6/N_2 mixtures which contain more than 40 to 50% of SF_6 showed little additional improvement in V_s . In the

Table 6. Effect of Negative Ion Resonances on Breakdown^{a,b}

Percentage of Component Gas					Slope (kV/atm-mm)	Intercept (kV)	(V _s) ^c _R
<u>C₄F₆</u>	<u>SF₆</u>	<u>H₂</u>	<u>N₂</u>	<u>CO</u>			
10		90			4.39	0.82	0.55
10			90		6.18	0.66	0.73
10				90	6.71	1.02	0.82
33		67			8.76	0.68	1.01
33			67		8.93	1.41	1.10
33				67	10.74	0.61	1.22
66		34			15.05	0.55	1.66
66			34		14.16	0.22	1.52
66				34	16.12	0.49	1.76
<hr/>							
	10	90			3.27	0.69	0.40
	10		90		4.83	1.18	0.60
	10			90	5.75	1.13	0.71
	33	67			4.79	1.13	0.59
	33		67		6.55	0.83	0.78
	33			67	7.18	1.04	0.86
	66	34			6.70	0.83	0.80
	66		34		7.56	1.03	0.91
	66			34	8.28	0.66	0.96
<hr/>							
100					17.55	2.00	2.09
	100				8.49	0.87	1.00
		100			1.55	1.30	0.25
			100		2.74	1.56	0.40
				100	3.52	1.80	0.50

^aFrom Ref. 4.^bTotal pressure 2 atm; sphere-plane electrode geometry.^cBreakdown strength relative to SF₆ of 1.

Fig. 7. a. Breakdown voltages for SF_6/N_2 mixtures with cylindrical electrode radii 0.4 and 2 cm. (o) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data. b. Breakdown voltages for $\text{c-C}_4\text{F}_8/\text{N}_2$ mixtures with cylindrical electrode radii 0.4 and 2 cm. (o) inner electrode at positive potential, ($\bullet$) inner electrode at negative potential, (Δ) normalized uniform field data.

nonuniform fields of concentric cylinder geometries, the V_s vs % SF_6 curves exhibit less of this saturation. From similar data⁴ using inner electrode radii of 1.4, 0.75, and 0.4 cm, each inside the outer cylinder of inner radius of 2 cm, it seems that the difference between the uniform and nonuniform field values of V_s increases with increasing field inhomogeneity. This could be attributed to the fact that the electron energy distribution function is shifted to higher energies in the case of nonuniform fields and to remove the same number of electrons more SF_6 is needed because the electron attachment cross section for SF_6 is small for electrons with energies $\gtrsim 0.4$ eV (see Fig. 3). Consistent with this interpretation are the data in Fig. 7b on $\text{c-C}_4\text{F}_8/\text{N}_2$ where it is seen that when the uniform field data on V_s vs % $\text{c-C}_4\text{F}_8$ in N_2 are normalized to the nonuniform field data on the same system, minor differences are observed and practically no saturation effect is evident in either. The superior behavior of $\text{c-C}_4\text{F}_8$ compared with SF_6 is attributed to the fact that the electron attachment cross section for this molecule extends to higher energies than that for SF_6 (Fig. 3). This explanation is, however, tentative and requires further scrutiny. Our experiments so far indicate that in the nonuniform fields of concentric cylinders, $\text{c-C}_4\text{F}_8$, C_4F_8 , and C_4F_6 continue to be far superior insulating gases to SF_6 . Further work in this area and on the effect of surface roughness and electrode material on V_s is in progress at our laboratory.

ENVIRONMENTAL ASPECTS OF DIELECTRIC GASES; ANALYSIS OF BREAKDOWN PRODUCTS OF NEW GAS INSULATORS

An important consideration in the study of gaseous dielectrics is that of decomposition of the original gas/gas mixture. Decomposition results in possible loss of dielectric strength and in the possible formation of products which may be harmful to the system, to the environment or to both. Knowledge of the extent and nature of the decomposition products is necessary for any possible chemical intervention to neutralize the toxic or otherwise harmful products formed.

Presently at our laboratory a program is underway to systematically study the processes which lead from the initial electron impact induced fragmentation to the final long-lived products formed after breakdown.

There are essentially three aspects to this program: (1) determination of the initial products (parent ions, fragment ions, and radicals) resulting from single electron-molecule collisions as a function of electron energy by application of time-of-flight mass spectrometry; (2) analysis of decomposition products by a combination of gas chromatography and mass spectrometry; and (3) a study of the intermediate ion-molecule reactions which lead from the initial to the final products by high pressure mass spectrometry.

As an example to this approach, we have studied¹² C_4F_6 (perfluoro-2-butyne). The time-of-flight mass spectrum of C_4F_6 shows that low-energy ($\lesssim 10$ eV) electron impact results predominantly in the formation of $C_4F_6^-$ ions, contributing >98% of all negative ions produced in this energy range. The remaining (<2%) ions consist of $C_3F_3^-$, F^- , and CF_3^- (see Table 7 and Fig. 8 for the relative intensity and energy dependence of these ions). It is thus indicated by these findings that C_4F_6 is not easily decomposed under electron bombardment. The resistance to fragmentation, seen in the C_4F_6 molecule, can be more fully appreciated when it is compared with the electron impact induced fragmentation of another good dielectric, namely, C_4F_8 (perfluorobutene-2). Perfluorobutene-2 (C_4F_8) exhibits far more extensive fragmentation (see Table 7) including the formation of $C_4F_7^-$, $C_4F_6^-$, $C_3F_5^-$, $C_3F_3^-$, $C_2F_3^-$, CF_3^- , and F^- ions with F^- being the most abundant ion in the vicinity of 5 eV. Quite unlike the results for C_4F_6 , the negative ion fragments $C_4F_7^-$ and $C_4F_6^-$ were produced at near-zero energies in the case of C_4F_8 . From the standpoint of initial electron impact induced fragmentation, C_4F_6 appears to be quite stable.

The problem of tracing the reaction pathways leading from the initial ion fragments to the final stable products is very complex, requiring a study of the ion-molecule reaction processes using high pressure mass spectrometry. This phase of our work in which the intermediates will be identified will be undertaken in the near future.

The last step of the decomposition problem lies in the identification and quantification of the products formed in gases which have been subjected to electrical breakdown. To accomplish this, gases which have

Table 7. Parent and Fragment Negative Ions Produced in C_4F_6 (Perfluoro-2-butyne) and C_4F_8 (Perfluorobutene-2) by Electron Impact

Negative Ion	Position of Maximum Ion Intensity	Relative Peak Ion Intensity
<u>C_4F_6 (perfluoro-2-butyne)</u>		
$C_4F_6^{-*a}$	~ 0.0	1000
$C_3F_3^-$	1.5	2.4
	5.0	4.0
CF_3^-	5.9	0.2
F^-	5.3	3.1
<u>C_4F_8 (perfluorobutene-2)</u>		
$C_4F_8^{-*a}$	~ 0.0	1000
	4.1	~ 0.5
	7.4	~ 0.3
$C_4F_7^{-*a}$	~ 0.0	9.5
$C_4F_6^{-*a}$	~ 0.0 (shoulder)	
	~ 0.7	1.5
$C_3F_5^{-*a}$	2.3	0.8
	4.2	2.3
$C_3F_3^-$	5.1	0.9
$C_2F_3^-$	5.4	0.4
CF_3^-	5.3	1.3
F^-	5.2	26.7

^aThese ions were found to be metastable with autodetachment lifetimes $>10^{-5}$ sec.

been sparked under controlled conditions have been analyzed in a gas chromatograph followed by an ionization mass spectroscopy detection system. Preliminary work on a pure sample of C_4F_6 shows that the nontoxic¹³ gases CF_4 (perfluoromethane), C_2F_4 (perfluoroethylene), and

Fig. 8. Negative ion intensity as a function of electron energy for C₄F₆ (perfluoro-2-butyne). Except where noted the spectra were taken without the retarding potential difference (RPD) method.

C₂F₆ (perfluoroethane) are produced. The extent of decomposition of the dielectric as a function of the energy delivered to the system for both unitary and multicomponent gas mixtures is under investigation.

TOXICITY AND CARBON DEPOSITS

A comment on the toxicity and carbon deposits of sparked gases is in order. The toxicity of fluorocarbon compounds varies enormously with relatively small changes in their structure. Thus *c*-C₄F₈ is nontoxic (an 80% mixture with 20% oxygen substituted for air and breathed for four hours did not affect rats¹⁴), while *iso*-C₄F₈ (perfluoroisobutene) at 0.5 parts per million in air was found to be lethal to animals if breathed for four hours.¹⁵

Each new compound recommended for large-scale commercial use must be individually subjected to prior testing for toxicity. In such toxicity tests care must be taken to ensure that various compounds used as precursors in the manufacturing of fluorocarbons are eliminated, since such compounds often tend to be very toxic and trace amounts—which could be eliminated with careful manufacturing procedures—may be overlooked in small-scale laboratory preparations and can thus lead to erroneous conclusions as to the toxicity of a compound. For example, C_4F_6 samples can be contaminated with $C_4F_6Cl_2$ —a known toxic compound used in the preparation of C_4F_6 —which can be eliminated by a careful manufacturing procedure.

Another major problem connected with the use of perfluorocarbon compounds in electrical apparatus is the formation and deposition of carbon from the gas under an arc. This carbon can settle on insulators and short them out. Two possible ways to overcome this problem are:

(1) appropriate designs of insulators which can relieve the effect of the carbon deposits on the insulators and (2) the use of SF_6 and N_2 (and perhaps other gases) in mixtures with perfluorocarbons. Such mixtures (e.g., $C_4F_6/SF_6/N_2$) can greatly reduce carbon deposits while increasing the dielectric strength above that of SF_6 (see Ref. 4).

REFERENCES

1. J. S. Pearson and J. A. Harrison, J. Phys. D (Appl. Phys.) 2, 77 (1969).
2. H. Winkelkemper, Z. Krasucki, J. Gerhold, and T. W. Dakin, Electra 52, 67 (1977).
3. L. G. Christophorou, D. R. James, R. Y. Pai, M. O. Pace, R. A. Mathis, D. W. Bouldin, and D. E. Tittle, High Voltage Research, Third Quarterly Report, Oak Ridge National Laboratory Report ORNL/TM-5806, February 1977.
4. L. G. Christophorou, D. R. James, R. Y. Pai, R. A. Mathis, M. O. Pace, D. W. Bouldin, A. A. Christodoulides, and C. C. Chan, High Voltage Research, Semiannual Report, Oak Ridge National Laboratory Report ORNL/TM-6113, November 1977.

5. L. G. Christophorou, "Elementary Electron-Molecule Interactions and Negative Ion Resonances at Subexcitation Energies and Their Significance in Gaseous Dielectrics," paper presented at the International Conference on Phenomena of Ionized Gases, Berlin, September, 1977; Conference Proceedings, Vol. II (in press).
6. A. A. Christodoulides, R. Y. Pai, and L. G. Christophorou, Electron Attachment to Dielectric Gases (to be published).
7. L. G. Christophorou, Atomic and Molecular Radiation Physics, Wiley-Interscience, New York, 1971.
8. G. J. Schulz, Rev. Mod. Phys. 45, 423 (1973).
9. L. G. Christophorou, "Interactions of O₂ with Slow Electrons," paper presented at the International Conference on Singlet Oxygen and Related Species in Chemistry and Biology, Pinawa, Canada, August 1977; Photochem. Photobiol. (in press).
10. L. G. Christophorou, M. W. Grant, and D. L. McCorkle, Advances in Chemical Physics 36, 413 (1977).
11. G. J. Schulz, Phys. Rev. A 135, 988 (1964).
12. I. Sauers, L. G. Christophorou, and J. G. Carter (to be published).
13. W. Braker and A. L. Mossman, Matheson Gas Data Book, Fifth Edition, Matheson Gas Products, New Jersey, 1971.
14. J. W. Clayton, Jr., M. A. Delaplane, and D. B. Hood, Ind. Hyg. J. 21, 382 (1960).
15. J. W. Clayton, Jr., J. Occup. Med. 4, 262 (1962).

INTERNAL DISTRIBUTION

1-2.	Central Research Library	63.	H. M. Long
3.	Document Reference	64.	R. A. Mathis
4-6.	Laboratory Records	65.	M. M. Menon
7.	Laboratory Records, R.C.	66-67.	M. O. Pace
8.	ORNL Patent Office	68-69.	R. Y. Pai
9.	M. A. Baker	70.	H. Postma
10.	R. D. Birkhoff	71.	C. R. Richmond
11.	D. W. Bouldin	72.	M. W. Rosenthal
12.	J. G. Carter	73.	H. C. Schweinler
13-57.	L. G. Christophorou	74.	S. W. Schwenterly
58.	H. H. Hubbell	75.	J. H. Whealton
59-60.	D. R. James	76.	H. A. Wright
61.	C. M. Jones	77.	N. F. Ziegler
62.	S. V. Kaye	78.	A. Zucker

EXTERNAL DISTRIBUTION

79. D. Allen, Division of Electric Energy Systems, Department of Energy, Washington, D.C. 20545
80. K. Dimoff, Institut National de la Recherche Scientifique, Universite du Quebec, Case Postale 1020, Varennes, Quebec, JOL 2P0, Canada.
81. J. Gracia, Research and Technical Support Division, Oak Ridge Operations, Department of Energy, Oak Ridge, Tennessee 37830.
82. Director, Research and Technical Support Division, Oak Ridge Operations, Department of Energy, Oak Ridge, Tennessee 37830.
83. O. Farish, Department of Electrical Engineering, University of Strathclyde, Glasgow, G1, 1XW, Scotland.
84. R. W. Flugum, Division of Electric Energy Systems, Department of Energy, Washington, D.C. 20545.
- 85-95. T. F. Garrity, Division of Electric Energy Systems, Department of Energy, Washington, D.C. 20545.
96. J. M. Googe, Department of Electrical Engineering, The University of Tennessee, Knoxville, Tennessee 37916.
97. D. Mayhew, Office of the Controller, Department of Energy, Washington, D.C. 20545.
98. J. McKeown, Assistant Administrator for Conservation, Department of Energy, Washington, D.C. 20545.
99. J. J. Phillips, Tennessee Valley Authority, 1310 Commerce Union Bank Building, Chattanooga, Tennessee 37401.
100. V. Tahlilani, Electric Power Research Institute, P.O. Box 10412, Palo Alto, California 94303.
101. J. P. Vora, Division of Electric Energy Systems, Department of Energy, Washington, D.C. 20545.
- 102-128. Technical Information Center.