DOE/PC/90055--T3

TECHNOLOGY DEVELOPMENT FOR IRON FISCHER-TROPSCH CATALYSTS

Contract DE-AC22-90PC90055

Robert R. Frame
UOP
25 E. Algonquin Road
Des Plaines, Illinois

DOE/PC/90055--T3

DE92 018441

Technical Progress Report No. 4
6/26/91 - 9/26/91

Contract Objective

The objectives of this contract are to develop a technology for the production of active and stable iron (Fe) Fischer-Tropsch catalysts for use in slurry-phase synthesis reactors and to develop a scaleup procedure for large-scale synthesis of such catalysts for process development and long-term testing in slurry bubble-column reactors. With a feed containing hydrogen (H_2) and carbon monoxide (CO) in the molar ratio of 0.5 to 1.0 to the slurry bubble-column reactor, the catalyst performance target is 88% CO + H_2 conversion at a minimum space velocity of 2.4 NL/hr/gFe. The desired sum of methane and ethane selectivities is no more than 4%, and the conversion loss per week is not to exceed 1%.

Contract Tasks

- Task 1.0: Catalyst development
 - 1.1: Technology assessment
 - 1.2: Precipitated catalyst preparation method development
 - 1.3: Novel catalyst preparation methods investigation
 - 1.4: Catalyst pretreatment
 - 1.5: Catalyst characterization
- Task 2.0: Catalyst testing
- Task 3.0: Catalyst aging studies
- Task 4.0: Preliminary design and cost estimate of a catalyst synthesis facility

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

js

Task 1.5

Progress has been made toward developing methodology to use magnetic susceptibility measurements to characterize fresh and used catalysts. The use of magnetic measurements is based on the realization that the main component of the catalyst is iron, which is one of the three ferromagnetic elements (the other two are cobalt and nickel). Hopefully, the magnetic measurements will give information on the electronic nature of the catalyst.

Samples were analyzed as recovered from the reactor (in a product wax matrix). Differences were found in the wax-containing and wax-free samples. The wax-containing samples are believed to be representative of the actual operating catalyst because they are less likely to change on standing after removal from the autoclave.

Pure compounds of iron have unique magnetic properties. These pure iron samples have been analyzed as reference: α and γ $\text{Fe}(\text{OH})_3$, FeO , Fe_3O_4 , Fe_2O_3 , Fe^0 . Pure iron carbides are also available and will be analyzed.

Two types of magnetic measurements are of interest in this work. The first is the magnetization, σ , as a function of temperature; the other is magnetization as a function of magnetic field at a given temperature (hysteresis). Curves are usually obtained over a predetermined range of the variable (either temperature or magnetic field) by going first in one direction (e.g., up in temperature) and then in other direction (e.g., down in temperature) to the original value. Much can be learned from magnetic measurements. For instance, a uniform hysteresis curve indicates uniform distribution of the catalytic components (e.g., Fe, copper (Cu), and potassium (K), and eventually carbidic carbon as it builds up during use).

Two methods of performing the magnetic measurements were considered: vibrating sample magnetometer and Faraday magnetometer. Both methods are well established. The first is automated and easier to do but is the least sensitive of the two methods. In this work, magnetization as a function of temperature is measured. Liquid helium cryostat is used, and magnetization is measured between 50 K and 250 K.

Many end-of-the-run catalyst samples have been analyzed. In addition, during Run 32, samples were removed at various times between 1 and 47 hr on-stream. Conversions and selectivities from this run (Plant 700B, Run 32) were summarized in Quarterly Report No. 3 for this contract. The magnetic measurements on the Run 32 samples determined that the initial iron phase was iron hydroxide ($\text{Fe}(\text{OH})_3$) and the first iron transformation during the reduction was to iron oxide, FeO (Figure 1). The next iron phase appears to be yet unidentified carbide. Figure 2 illustrates that the magnetization behavior correlates well with CO conversion.

Task 2.0

A uniform lot of iron and copper oxide precursor (752R19B9) was prepared in the precipitation plant 752. From this lot, five catalysts were prepared, each with a different level of K. These crystals were evaluated under similar conditions to determine the effect of K level on conversion and product selectivity.

Five different runs (Runs 35 to 39) were conducted in the slurry autoclave pilot plant. The catalyst testing procedure and conversion-selectivity calculations were described in the technical progress report covering the period from 4/1/90 to 6/30/90 of the previous contract DE-AC22-87PC79812. The catalytic performance for these five runs are summarized in Figures 3 to 26. The specific test conditions are indicated in these performance data summaries.

In all runs, 72.7 g of catalyst was loaded with 290 g of a C_{30} oil obtained from the Ethyl Corporation. The catalyst was activated in the presence of a feed mixture containing H_2 and CO in the molar ratio of 0.7. The pretreatment consisted of 12 hr with 2 NL/hr/gFe of feed at 280°C and 153 psig. During the remainder of the run, the feed rate was 2.4 NL/hr/gFe, the temperature was 265°C , and the pressure was 290 psig. The stirrer speed in the autoclave was maintained at 1,100 RPM throughout the run.

Runs 35 to 39

Figures 3 to 26 show conversions and selectivities vs. hours on-stream for each run. The catalysts used in these runs had increasing levels of K in this order: Run 35, 36, 37, 39, and 38. All runs

lasted at least 150 hr, which was long enough for the conversions and selectivities to attain steady state.

So that run-to-run comparisons could be made, each run's conditions were kept similar. However, in Run 39 after line-out, a decrease in space velocity caused an increase in the conversion. This change was made to determine product selectivities at the higher conversion. Figure 27 is a conversion-selectivity plot constructed from the data at two space velocities. Near the end of Run 39, isobutane ($i\text{-C}_4\text{H}_{10}$) was introduced into the feed to determine whether it could be converted into hydrocarbon product. Figure 28 shows that $i\text{-C}_4\text{H}_{10}$ was observed in the product gas shortly after it was introduced into the feed. The amount of $i\text{-C}_4\text{H}_{10}$ in the product gas was enough to indicate that its conversion was negligible at best.

Comparison of Runs 35 to 39

Figures 29 to 37 compare conversions and selectivities after line-out for Runs 35 to 39. Table 1 below summarizes the line-out performance of these runs.

Table 1
Comparison of Runs 35-39

Run No.	Catalyst	Feed Rate NL/Hr/g Fe	Line-out Results		
			H ₂ /CO (molar)	CO Conv. (%)	CH ₄ Selec. (mole%)
35	752R19B9A (100Fe:2.05Cu:1.16K)	2.7	0.90	73	5.3
36	752R19B9B (100Fe:2.31Cu,1.72K)	2.4	0.90	73	5.4
37	752R19B9C (100Fe:2.10Cu,2.06K)	2.4	1.0	73	4.2
39	752R19B9E (100Fe:2.46Cu,2.70K)	2.4	0.75	46	3.0
		1.2	1.03	73	3.5
38	752R19B9D (100Fe:2.13Cu,3.85K)	2.4	0.75	55	2.7

Figure 29 is a plot of line-out CO conversion as a function of the amount of K on the catalyst. The catalysts with higher K level were less active.

Three traps are used to capture products from the slurry autoclave plant. The traps are in series and operate, respectively, at the following temperatures: 160°C, 0°C, and -78°C. The weights in these traps can be used to crudely estimate the nature of the Fischer-Tropsch product because the relative amounts in the three traps are roughly related to the molecular weight distribution of the condensable products. Figure 30 is a plot of the relative amounts of liquid in the three traps as a function of the amount of K on the catalyst (from lowest K level, Run 35, to highest K level, Run 38). Catalysts with high levels of K favor heavy products.

Line-out methane (CH_4) selectivities are plotted in Figure 31 for the four runs in which such selectivities are available at 72 to 74% CO conversion. The plot, which is of CH_4 selectivity vs. H_2/CO molar ratio, indicates that CH_4 selectivity is lower at the higher H_2/CO ratios. The CH_4 selectivity also decreased as the catalyst K level increased. The best catalyst from the combined standpoints of activity and low CH_4 selectivity was the one used in Run 37.

Figures 32 to 34 show olefin-to-paraffin ratios for C_2 to C_4 products. This ratio is important because olefinic rather than paraffinic products are desired. Again the best catalyst was the one used in Run 37: catalyst 752R19B9C. It was very active and also produced olefinic C_2 , C_3 , and C_4 products. The olefin-to-paraffin ratio increased as the K level increased.

The C_1 to C_4 hydrocarbon selectivities (paraffins plus olefins) for Runs 35 to 37 and Run 39 are shown in Figure 35. The data are from after line-out at 73% conversion. The superiority of the catalyst 752R19B9C, which was used in Run 37, to the other catalysts is again apparent: the total C_1 to C_4 selectivity was low in spite of the fact that Run 37 catalyst was similar in activity to those used in Runs 35 and 36 (catalysts 752R19B9A and 752R19B9B, respectively). The C_2 to C_4 alcohol selectivities for these four runs are shown in Figure 36. In this case, the Run 37 catalyst (752R19B9C) was again similar to the lower activity Run 39 catalyst (752R19B9E).

One goal of this work is to provide Schulz-Flory plots of the data for carbon nos. up to 250. Figure 37 is a Schulz-Flory plot of Run 35, which resulted from a combination of off- and on-line gas chromatography data along with off-line gel-phase chromatography (GPC) for the higher carbon numbers. It is a summation of all products (olefins, paraffins, alcohols, and aldehydes) over the entire run. The end-of-run autoclave contents (wax) are also included. The peaks centered around carbon no. 27 are from the C_{30} oil used in the autoclave at the start of the run. This oil is

branched and reports at less than carbon no. 30 in the GPC protocol, which looks for straight chains. The discontinuity around carbon no. 50 is unexpected and is being reviewed.

Conclusions

The performance of the slurry-phase iron and copper oxide-based catalyst used in the studies depends markedly on the amount of K present in the catalyst. Five catalysts were studied. Each catalyst was prepared from a separate aliquot of the same iron and copper oxide by impregnation using potassium carbonate followed by calcination. Each of the five catalysts contained a different amount of K.

Three lowest potassium-level catalysts (752R19B9A, B, and C) had about the same activity and were more active than the two highest potassium-level catalysts (752R19BD and E). Catalyst 752R19B9C, evaluated in Plant 700B, Run 37, was judged to be the best among all five catalysts. It retained the high activity of the two lower potassium-level catalysts (752R19B9A and B) and exhibited low selectivity to methane and ethane as did the two highest potassium-level catalysts (752R19B9D and E).

Plans for the Next Quarter

A large sample of catalyst will be prepared from the same iron and copper oxide (752R19B9) precursor used in the potassium-level study described previously. Potassium will be impregnated at the same level as on the catalyst judged to be the best above, namely catalyst 752R19B9C used in Plant 700B, Run 37. Aliquots of this large sample of catalyst will be used to begin studies on the effect of changes in the catalyst pretreatment procedure on catalyst activity, selectivity, and stability (Contract Task 1.4).

FIGURE 1
CHANGE IN MAGNETIZATION AS A FUNCTION OF RUN TIME

Data are for catalyst samples withdrawn during Run 32.

FIGURE 2
CORRELATION BETWEEN CO CONVERSION AND MAGNETIZATION

Magnetization data are corrected for wax content.

Figure 3. Data Summary for Run 35: H_2/CO Usage Ratio

Figure 4. Data summary for Run 35: H₂ Conversion

Figure 5. Data Summary for Run 35: Ethane Selectivity

Figure 6. Data Summary for Run 35: Methane Selectivity

Figure 7. Data Summary for Run 35: Ethylene Selectivity

Figure 8. Data Summary for Run 36: H₂ Conversion

Figure 9. Data Summary for Run 36: H_2/CO Usage Ratio

Figure 10. Data Summary for Run 36: Methane Selectivity

Figure 11. Data Summary for Run 36: Ethane Selectivity

Figure 12. Data Summary for Run 36: Ethylene Selectivity

Figure 13. Data Summary for Run 37: H₂ Conversion

Figure 14. Data Summary for Run 37: H₂/CO Usage Ratio

Figure 15. Data Summary for Run 37: Methane Selectivity

Figure 16. Data Summary for Run 37: Ethane Selectivity

Figure 17. Data Summary for Run 37: Ethylene Selectivity

Figure 18. Data summary for Run 38: H₂ Conversion

Figure 19. Data Summary for Run 38: Methane Selectivity

Figure 20. Data Summary for Run 38: H_2/CO Usage Ratio

Figure 21. Data Summary for Run 38: Ethylene Selectivity

Figure 23. Data Summary for Run 39: Methane Selectivity

Figure 24. Data Summary for Run 39: H₂/CO Usage Ratio

Figure 25. Data Summary for Run 39: Ethylene Selectivity

Figure 26. Data Summary for Run 39: Ethane Selectivity

FIGURE 27
SELECTIVITY TO LIGHT HYDROCARBONS - RUN 39

Data from 120-130 HRS--just before and just after feed rate was changed.
Run Conditions: 265 C, 290 psig, 0.7 H₂:CO

FIGURE 28
EFFECT OF ISOBUTANE ADDITION TO FEED - RUN 39

Feed (Mole %) : Ar: 5.9, H2: 38.9, CO: 54.4, i-C4: 0.8

FIGURE 29
EFFECT OF K LEVEL ON LINE-OUT CONVERSION

■ Run 35 + Run 36 × Run 37 □ Run 38 × Run 39

Feed rate: 2.4 or 2.7 NL/hr/g Fe, Temp.: 265 C

FIGURE 30
EFFECT OF CATALYST ON LIQUID PRODUCT DISTRIBUTION

Excess liquid in the reactor, over that present at the start-up, was added to the weight of the hot trap.

FIGURE 31
EFFECT OF H₂/CO RATIO ON METHANE SELECTIVITY

▪ RUN 35 + RUN 36 * RUN 37 □ RUN 39

CO Conversion: 72-74%, Run Temp.: 265 C

FIGURE 32
EFFECT OF K LEVEL ON C2 OLEFIN TO PARAFFIN RATIO

■ RUN 35 + RUN 36 * RUN 37 □ RUN 39

73 % CO Conversion, 265 C, 130 hr on-stream

FIGURE 33
EFFECT OF K LEVEL ON C3 OLEFIN TO PARAFFIN RATIO

73 % CO Conversion, 265 C, 130 hr on-stream

FIGURE 34
EFFECT OF K LEVEL ON C4 OLEFIN TO PARAFFIN RATIO

73 % CO Conversion, 265 C, 130 hr on-stream
Only 1-butene and n-butane were observed in the product.

FIGURE 35
EFFECT OF CATALYST ON LIGHT HYDROCARBONS SELECTIVITY

73 % CO Conversion, 265 C, 130 hr on-stream

FIGURE 36
EFFECT OF CATALYST ON LIGHT ALCOHOL SELECTIVITY

73 % CO Conversion, 265 C, 130 hr on-stream

Figure 37. Schulz-Flory Plot for Run 35 Data

Carbon number includes olefins, paraffins, alcohols, and aldehydes

END

**DATE
FILMED
3 / 31 / 93**