PRODUCTION AND EVALUATION OF a-GaAs SOLAR CELLS

QUARTERLY TECHNICAL PROGRESS REPORT
FOR THE PERIOD
NOVEMBER 1, 1979 - JANUARY 31, 1980

MASTER

William Paul, Principal Investigator
Dilip K. Paul, Staff Scientist

March 1980

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Work Performed Under Contract DE-AC03-79ET23036

HARVARD UNIVERSITY
DIVISION OF APPLIED SCIENCES
CAMBRIDGE, MASSACHUSETTS 02138

ACCEPTANCE BOND

50% COTTON FIBER USA

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States nor any agency thereof, nor any of their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for any third party's use or the results of such use of any information, apparatus, product or process disclosed in this report, or represents that its use by such third party would not infringe privately owned rights.

PRODUCTION AND EVALUATION OF a-GaAs SOLAR CELLS

QUARTERLY TECHNICAL PROGRESS REPORT
FOR PERIOD NOVEMBER 1, 1979 - JANUARY 31, 1980

WILLIAM PAUL
Principal Investigator

DILIP K. PAUL
Staff Scientist

MARCH 1980

HARVARD UNIVERSITY
DIVISION OF APPLIED SCIENCES
CAMBRIDGE, MASSACHUSETTS 02138

PREPARED FOR THE
U.S. DEPARTMENT OF ENERGY
SOLAR ENERGY
UNDER CONTRACT DE-AC03-79ET23036

ABSTRACT

a-GaAs:H alloys have been prepared by r.f. sputtering in a mixture of argon and hydrogen at several partial pressures, substrate temperatures and r.f. powers. We report the results of a systematic investigation of the electrical and optical properties of these films. The effect of isothermal annealing on various electronic properties has also been investigated. Depth profiles of the impurity content derived from SIMS measurements are included.

DESCRIPTION OF PROJECT

The purpose of this project is i) to produce and dope a-GaAs alloys, principally with hydrogen, and ii) to evaluate their potential for low-cost solar cell material.

The approach adopted was to r.f. sputter GaAs in the presence of hydrogen or dopant gases such as PH_3 and B_2H_6 , and to vary the conditions of preparation such as substrate temperature, hydrogen partial pressure, argon sputtering gas pressure, sputtering rate and r.f. power. Subsequently, the films were to be characterized with regard to their chemical, structural, electronic and optical properties, and a model for the band structure, defect structure, transport and recombination properties was to be sought from these measurements. Evaluation of device potential was to be activated at an appropriate time after the films show promising properties as judged by the characterization schemes.

TABLE OF CONTENTS

<u>Section</u>	<u>Page</u>
ABSTRACT	i
DESCRIPTION OF PROJECT	ii
INTRODUCTION	1
ELECTRONIC PROPERTIES OF a-GaAs ALLOYS	1
1. Electrical Transport	3
2. Optical Properties	10
SIMS STUDY OF IMPURITIES AND DEPTH PROFILING OF HYDROGEN	13
SUMMARY OF CONCLUSIONS AND FUTURE PLANS	15
REFERENCES	16
DISTRIBUTION LIST	17

LIST OF FIGURES

Figure 1	page 2
Figure 2	4
Figure 3a	5
Figure 3b	6
Figure 4	7
Figure 5	9
Figure 6	11
Figure 7	12
Figure 8	14

INTRODUCTION

In the first quarterly report¹ we described the effects of hydrogen incorporation in r.f. sputtered amorphous GaAs on IR and Raman measurements, and also on the evolution of H₂ on heating. A preliminary discussion^{1,2} on the findings of other characterization schemes - electrical, optical, structural and compositional - was included. We present in this report the completed results of the first stage of our investigation of the electrical transport and optical absorption. The effects of the variation of deposition parameters such as r.f. power, partial pressures of argon and hydrogen, substrate temperature, etc., and also of post-deposition annealing treatment have been studied. In an attempt to prepare chemically pure material (impurity-free, especially from oxygen, as proposed in the previous quarterly report), we have adopted several changes in our deposition procedure. The secondary-ion-mass-spectrometric (SIMS) analysis of the impurity concentration in these films is also presented.

ELECTRONIC PROPERTIES OF a-GaAs ALLOYS

A description of the sample preparation technique and the sputtering apparatus/vacuum system has been given earlier.^{1,2} The samples were prepared with the following variable parameters: i) r.f. power (40-140 watts), ii) substrate temperature, T_s (up to 40°C), iii) partial pressure of hydrogen, p_H ($0 - 5 \times 10^{-3}$ Torr) and iv) partial pressure of argon, p_{Ar} ($5 \times 10^{-3} - 15 \times 10^{-3}$ Torr). A number of samples were deposited simultaneously in the same run for parallel experiments. The post-deposition annealing was performed at several temperatures in the isothermal mode, but for the same time duration. In order to study the effect of annealing time, a few samples were also annealed successively for longer duration at fixed temperatures. The temperature of annealing was chosen on the basis of our previous studies of the hydrogen evolution characteristics. Introducing hydrogen in an argon plasma changes its character. As the deposition process is dependent mainly on i) power, ii) plasma character and iii) geometry of the chamber, the rate of deposition is changed considerably by the constituent gases of the plasma. The dependences of the deposition rate on p_H and r.f. power are shown in Figure 1.

Figure 1. Effects of p_H and rf power on the deposition rate of amorphous GaAs alloys. Target size: 5 inches diameter; cathode to anode spacing: 3.5 inches. p_{total} is the sum of variable deposition parameters p_H and p_{Ar} .

1. Electrical Transport

Nichrome contacts evaporated on samples through suitable masks in a vacuum system (low 10^{-6} Torr) have been used for electrical transport measurements. The d.c. electrical conductivity was measured in a low temperature evacuated dewar using a Keithley electrometer (Model 602) and a Cary vibrating reed electrometer (Model 31). The experimental set-up is automated with a Dec PDP-1100 System. The conductivity measurements were usually performed in the four-probe configuration. Occasionally, measurements were repeated with a two-probe geometry. Thermoelectric power (TEP) was measured in a special TEP set-up³ on samples prepared specifically for this purpose. Whenever possible cross checks between conductivity, TEP and optical data were made on the same sample.

Figure 2a shows the effect of p_H on the temperature dependence of the electrical conductivity in as-deposited samples. The effect of successive isothermal annealing at different temperatures on these samples is shown in Figures 2b and 2c, where the effects of one-hour annealing each, at 100 and 150°C, respectively, are presented. Similar measurements have been done on films deposited at different p_{Ar} , r.f. power and T_s . A summary of these data is given in Figures 3a and 3b, where the effects of the deposition rate, p_H/p_{total} and isothermal annealing treatment on the electrical activation energy in the high temperature region, E_G , and room temperature conductivity, σ_{RT} , have been shown explicitly. Figure 4 shows typical thermopower results. It is to be noted from Figures 2b and 2c that, unlike in a-Si:H, the electrical conduction in a-GaAs:H does not show a single activated process for the full range of temperature investigated here (425 to 100 K). However, if we choose to analyze the temperature dependence of electrical conductivity by activated mechanisms, we may identify two regions of activated conduction, one at high temperature and the other at room temperature and below. In order to find these energies, we have given a least square fit (error less than $\pm 0.5\%$) to the conductivity data (typically two to three orders of magnitude) in the respective temperature ranges. The electrical activation energy in the low temperature region is typically ~ 0.17 eV. Using this two-band model, both TEP and conductivity data have been analyzed.

Figure 2. The temperature dependence of the electrical conductivity: effects of p_H and isothermal annealing. (a) as-deposited, (b) annealed at 100°C for 1 hour, (c) annealed at 150°C for 1 hour. rf power: 140 Watt; $p_{Ar} = 10 \times 10^{-3}$ Torr.

Figure 3a. Room-temperature conductivity and electrical activation energy as a function of the deposition rate.

Figure 3b. Room-temperature conductivity and electrical activation energy as a function of the P_H/P_{total} . P_{total} is the sum of variable deposition parameters, p_H and p_{Ar} .

Figure 4. Typical thermopower data in a-GaAs alloys.

Several interesting observations can be made from the electrical transport results:

- i) The behavior of E_{σ} and σ_{RT} (Figures 2 and 3) suggests that the gap has been cleaned by the introduction of hydrogen. However, beyond a certain p_H , states are again introduced in the gap at higher p_H and/or p_{Ar} , giving rise to increased conduction. The spectral dependence of the optical absorption (Figure 5) confirms this trend.
- ii) Annealing at relatively low temperature ($T_A \sim 100^\circ\text{C}$) decreases σ and increases E_{σ} , depending on the initial hydrogenation (Figures 2b and 3). The effect of hydrogen evolution, if any, is not observable at this temperature.
- iii) High temperature annealing ($T_A \sim 150^\circ\text{C}$) increases σ . The characteristic at low temperature is modified considerably, as if additional states are being created by this annealing (Figures 2c and 3).
- iv) Subsequent annealing at still higher temperature (175°C and above, up to 240°C) results in a similar overall behavior. The high temperature data are apparently unaffected. There is, however, a slight increase in the conductivity at the low temperature region. Also, the slope of the temperature dependence is reduced. Annealing at the highest temperature (240°C) shows an overall increase in σ , but no change in temperature dependence behavior.

Based on observations (i) through (iv) we have definite evidence of an activated process with an energy in the range of (~ 0.17 eV). The associated density of states and the exact magnitude of this energy are controlled by the partial pressure of hydrogen in the sputtering atmosphere and the post-deposition annealing temperature. As seen in Figure 2, a moderate p_H and annealing treatment help in reducing these states. The complexity of the electrical transport may be attributed to several possibilities:

- i) different efficiencies of hydrogen incorporation at different p_H in the as-deposited films
- ii) losses or redistribution of hydrogen by evolution or diffusion at higher annealing temperature
- iii) removal and/or redistribution of defects by annealing.

The second and third possibilities have a number of important consequences, depending on the predominance of one over the other.

Figure 5. The absorption edge in a-GaAs:H for various p_H .
 Insert: α vs. $h\nu$ over a large energy range for a
 film deposited at high p_{Ar} .

2. Optical Properties

The optical constants (absorption coefficient and refractive index) have been evaluated from reflection and transmission measurements between 0.03 and 0.5 eV, using a Perkin Elmer double beam spectrophotometer (Model 567) with a resolution of 0.0002 eV. For higher photon energies (> 0.5 eV), a Cary double beam spectrophotometer (Model 14) with a resolution of 0.0003 eV was used. Besides the direct measurement of thickness by a Sloan Dektak, other methods,² such as positions of interference fringes, a thin-film optical constants program and an out-of-plane SEM picture have been used to estimate thickness.

Both the amplitude and the positions of the interference fringes have been used to calculate the refractive index, n_f , in the limit of $n_f \gg k_f$ for a given substrate of index n_s , at a specified wavelength, λ . The absorption coefficient $\alpha = 4\pi k_f / \lambda$ is given for the double beam geometry as⁴

$$\alpha = \frac{1}{t} \ln \left| \frac{1}{B} \left[A + \{A^2 + 2BT(1 - R_2 R_3)\}^{1/2} \right] \right|$$

where, $A = (1 - R_{af})(1 - R_{fs})(1 + R_{sa})$

$$B = 2T(R_{af}R_{fs} + R_{fs}R_{sa} - 2R_{af}R_{fs}R_{sa})$$

T is the transmittance, and R_{af} , R_{fs} and R_{sa} are the reflectances of air-film, film-substrate and substrate-air interfaces, respectively. For $n_f \gg k_f$, the R 's have been estimated from Fresnel's equation. We have also used, occasionally, a much more elaborate thin film optical constants program which requires two reflections, for the light incident on the film and on the substrate sides of the sample, and a transmission measurement to calculate n_f , k_f and t simultaneously.

The hydrogenated material shows much lower n_f . There is a tendency for n_f to become constant with increased p_H . The spectral response of the absorption edge (α vs. $h\nu$) for various p_H and p_{Ar} at fixed T_s and P_{rf} (Figure 5) shows edge shifts to higher photon energies with increased p_H . The optical properties are shown in Figure 6. The effects of annealing (several temperatures and times) are presented in Figure 7.

Figure 6. The effects of the sputtering gases p_H and p_{Ar} on the optical properties: as-deposited films. The photon energies E_{04} and E_g are defined respectively by the absorption coefficient, $\alpha = 10^4 \text{ cm}^{-1}$, and by the relation $(\alpha h\nu)^{1/2} = E(h\nu = E_g)$. p_{total} is the sum of variable deposition parameters, p_H and p_{Ar} .

Figure 7. The effect of isothermal annealing on the optical properties: variation with annealing time and temperature.

SIMS STUDY OF IMPURITIES AND DEPTH PROFILING OF HYDROGEN

The effect of impurities on the electronic properties of hydrogenated amorphous semiconductors is an active area of research. As the impurities may be incorporated in several ways during the film preparation process, we have undertaken a careful investigation of the actual films by SIMS (Charles Evans Associates, Los Angeles). Hydrogenated silicon samples investigated by a C_s^+ ion source show oxygen impurity at $1 \times 10^{20} \text{ cm}^{-3}$, with other impurities, e.g., N, C, Cl and F at 5×10^{19} , 3.4×10^{19} , 1.3×10^{17} and $5 \times 10^{16} \text{ cm}^{-3}$, respectively. Also, there was a concentration of impurities at the interface between the film and the substrate. The details for the amorphous silicon-hydrogen samples are given in DOE Quarterly Report No. DOE/ET/23037-2. We have not seen any oxygen-related vibrational optical absorption in a-GaAs:H films, as we do sometimes in a-Si:H films. Nevertheless, in view of the relative insensitivity of the IR absorption at a trace level, a comparable SIMS analysis on a-GaAs:H with a C_s^+ ion source may be in order to settle the possibility of oxygen contamination. However, in so far as other impurities are concerned, the SIMS results of the silicon films are of significance for the a-GaAs:H films also, particularly because the pre-deposition procedure, such as cleaning of substrates, sputter-etching of target, etc., and the gases and sputtering system are the source in both cases. For amorphous GaAs:H alloys we have done SIMS analysis using O^+ source and looked for the metallic impurities/constituents. These data are given in Figure 8, which also shows the depth-profiles of various elements. Significant amounts of Al ($\sim 10^{18} \text{ cm}^{-3}$) and Cr ($\sim 4 \times 10^{16} \text{ cm}^{-3}$) can be seen. This, however, is not surprising in view of the fact that the GaAs target is of high resistivity, which is usually obtained by Cr-doping. Also, even with 99.9999% purity, Al is the major impurity (0.1 ppm) in both Ga and As. The important results of the SIMS study are: i) uniformity of hydrogenation ($1.8 \times 10^{21} \text{ cm}^{-3}$) throughout the film thickness and ii) no build-up of contaminants at the film-substrate interface.

Figure 8. SIMS depth profiles. At an ion intensity of 1×10^6 counts/sec, each ion will have a concentration of $^1\text{H} \approx 9 \times 10^{22} \text{ cm}^{-3}$, $^{27}\text{Al} \approx 3 \times 10^{18} \text{ cm}^{-3}$ and $^{52}\text{Cr} \approx 8 \times 10^{18} \text{ cm}^{-3}$.

SUMMARY OF CONCLUSIONS AND FUTURE PLANS

The investigation of the electronic properties of amorphous GaAs:H alloys leads to the following conclusions:

(a) Hydrogen incorporation improves both the electrical and optical properties by reducing the density of defect states. However, the improvement is never as dramatic as in the case of amorphous Si:H alloys. It should be noted that the substrate T_s is limited to $T_s \leq 40^\circ\text{C}$ by the crystallization process, and even a-Si:H films do not display very good properties when deposited at low temperature.

(b) Both electrical and optical properties show non-monotonic behavior with p_H . A high p_H and/or p_{Ar} introduces states in the gap.

(c) Though thermal annealing, in general, is known to heal defects, yet hydrogen may evolve if the temperature is high. Thus more states may be created due to breaking up of already satisfied dangling bonds. Also, depending on the initial degree of hydrogenation and defect concentration/configurations, the material may show different trends with annealing (Figure 7). However, in the temperature range between 175 and 225°C, the properties become stabilized with no further apparent reduction of hydrogen content. Also, one important distinction can be made between annealed a-GaAs:H and a-Si:H. The deterioration of the properties due to hydrogen evolution by annealing in a-GaAs:H is not so dramatic as in a-Si:H.

(d) Amorphous GaAs:H alloys are of p-type with an $S \sim 0.88 \text{ mV}/^\circ\text{K}$ at room temperature. The optical gap (E_{04}) is $\sim 1.3 \text{ eV}$ for well-annealed films ($T_A \sim 150^\circ\text{C}$). The conductivity activation energies at the high and low T regions are ~ 0.65 and $\sim 0.17 \text{ eV}$, respectively. It appears that the Fermi level is situated approximately in the middle of the gap. We have band transport at high T , whereas the low T transport may be identified with defect states. The shape of the valence band edge is determined by the amount of hydrogen incorporation and the concentration of defect states.

(e) The depth profile of the constituents shows the homogeneity of the material deposited from a compound target by the sputtering process. Earlier SEM studies^{1,2} revealed that Ga and As atoms are equally incorporated in the film. The uniformity of the hydrogen concentration in the film is remarkable.

The immediate future work, as proposed earlier, will be continued along the following lines:

- (a) preparation of chemically pure material and continued characterization by SIMS analysis and IR observations
- (b) preparation at values of T_s , p_H , p_{Ar} and sputtering power designed to obtain material with lower gap state density
- (c) continued characterization by photoluminescence and photoconductivity of annealed samples
- (d) initiation of capacitance-voltage and Schottky diode measurements to give the gap state density and to evaluate the device possibilities.

REFERENCES

1. Quarterly Technical Progress Report, Department of Energy, DOE/ET/23036-1, November 1979.
2. D.K. Paul, J. Blake, S. Oguz and W. Paul, J. Non-Cryst. Solids 35 & 36, Parts I and II, 501 (1980).
3. Adam J. Lewis, Phys. Rev. B 13, 2565 (1976).
4. G.A.N. Connell and A.J. Lewis, Phys. Stat. Solidi (B) 60, 291 (1973).
5. Quarterly Technical Progress Report, Department of Energy, DOE/ET/23037-2, January 1980.

DISTRIBUTION LIST

L. Guttman
Argonne National Laboratory
Solid State Science Division
Argonne, IL 60493

Battelle Columbus Laboratories
Attn: Dr. Alfred E. Austin
505 King Avenue
Columbus, OH 43201

Brookhaven National Laboratory
Dept. of Energy & Environment
Attn: R.W. Griffith
Upton, NY 11973

JILA
University of Colorado
Attn: A. Gallagher
Boulder, CO 80309

Institute of Energy Conversion
University of Delaware
Attn: Dr. Vikram Dalal
1 Pike Creek Center
Wilmington, DE 19808

Duke University
Department of Mechanical Engineering
Attn: Dr. Franklin H. Cocks
Durham, NC 27706

EIC Corporation
Attn: Dr. R. David Rauh
55 Chapel Street
Newton, MA 02158

Harvard University
Division of Applied Sciences
Attn: Dr. William Paul
Pierce Hall
Cambridge, MA 02138

Lawrence Berkeley Laboratories
University of California
Attn: Dr. Nabil Amer
Berkeley, CA 94720

Lockheed Missiles & Space Co., Inc.
Research & Development Division
Attn: Art Jonath
3251 Hanover Street
Palo Alto, CA 94304

Massachusetts Institute of Technology
The Energy Laboratory
Attn: Dr. David Adler
Cambridge, MA 02139

Mobil Tyco
Attn: M. Cretella
16 Hickory Drive
Waltham, MA 02154

Nval Research Laboratory
X-Ray Optics Branch
Attn: D.A. Papaconstantopoulos
Washington, DC 20375

Naval Research Laboratory
Semiconductors Branch
Attn: C. Taylor
Washington, D.C. 20375

Naval Weapons Center
Michelson Laboratory
Attn: Dr. T.M. Donovan
China Lake, CA 93555

Pennsylvania State University
Attn: Dr. R.F. Messier
265 Materials Research Laboratory
University Park, PA 16802

RCA Corporation
Attn: Dr. David E. Carlson
P.O. Box 432
Princeton, NJ 08540

Xerox Corporation
Attn: R.A. Street
3333 Coyote Hill Road
Palo Alto, CA 94304

Jet Propulsion Laboratory
PV Data Center
Attn: Leau Ann Burrus
MS 50241
4800 Oak Grove Drive
Pasadena, CA 91103