AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 6

VOLUME I

SECTIONS 1 THROUGH 5

**TRANSFORMATIONS OF INORGANIC COAL
CONSTITUENTS IN COMBUSTION SYSTEMS**

Final Report

Under Contract No. DE-AC22-86PC90751

Editor: Dr. Joseph J. Helble, PSI Technology Company

Authors:

Dr. Joseph J. Helble, Dr. Srivats Srinivasachar,
Dr. Gerald Wilemski, and Dr. Arthur A. Boni
PSI Technology Company

Dr. Shin-Gyoo Kang, Prof. Adel F. Sarofim, Dr. Karl A. Graham, and Prof. Janos M. Beér
Massachusetts Institute of Technology

Prof. Thomas W. Peterson, Prof. Jost O.L. Wendt,
Mr. Neal B. Gallagher, and Mr. Larry Bool
University of Arizona

Prof. Frank E. Huggins, Prof. Gerald P. Huffman,
Dr. Naresh Shah, and Mr. Anup Shah
University of Kentucky

Prepared for:

U.S. DEPARTMENT OF ENERGY
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236-0940

November 1992

TABLE OF CONTENTS

<u>Section No.</u>	<u>Page No.</u>
1. EXECUTIVE SUMMARY	1-1
2. INTRODUCTION AND OVERVIEW OF PROGRAM TASKS	2-1
3. TASK 2 - COAL SELECTION, PREPARATION, AND CHARACTERIZATION (PSIT)	3-3
3.1 Background	3-3
3.2 Coal Selection, Acquisition, and Distribution	3-5
3.3 Description and Characterization of Phase I and II Coals	3-6
3.3.1 Illinois #6 - Spherical Oil Agglomeration (SOAP)	3-6
3.3.2 Kentucky #9 and Pittsburgh #8 - Molten Caustic Leach (Gravimelt)	3-8
3.3.3 Loy Yang 1953 Australian Brown Coal	3-13
3.3.4 Kentucky #9/Eagle Butte Blend	3-13
3.4 Summary of Phase I and Phase II Coal Analytical Data	3-15
3.5 Summary of Coal Mineralogical Analysis by CCSEM	3-15
3.6 References	3-24
4. CHARACTERIZATION BY ADVANCED ANALYTICAL TECHNIQUES (UKY)	4-3
4.1 Introduction	4-3
4.2 Experimental Techniques and Procedures	4-5
4.3 Coal Analysis	4-10
4.4 CCSEM Analysis of Pure Mineral Compounds	4-12
4.5 Ash Analysis	4-13
4.5.1 CCSEM Data for Ash Samples from the Phase I Coals	4-13
4.5.2 CCSEM Results for Ash Samples from Illinois #6 Parent and SOAP-Cleaned Coals	4-17
4.5.3 CCSEM Results for Ash Samples from Beulah Lignite Coal	4-18
4.5.4 CCSEM Results for Ash Samples from Loy Yang Coal	4-20
4.5.5 CCSEM Results for Ash Samples from Ion-Exchanged Potassium-Loaded Beulah Lignite Coal	4-22
4.5.6 Ceramic tube deposition samples from SECV runs	4-23
4.5.7 Mössbauer Spectroscopy Results for Selected Ash Samples	4-25

TABLE OF CONTENTS (Continued)

<u>Section No.</u>	<u>Page No.</u>
4.5.8 XAFS Spectroscopy Results	4-27
4.6 References	4-33
5. FUNDAMENTAL STUDIES OF MINERAL MATTER VAPORIZATION AND RESIDUAL ASH FORMATION (MIT)	5-3
5.1 Background	5-3
5.2 Experimental Apparatus	5-4
5.2.1 Laminar, Entrained-Flow Reactor	5-4
5.2.2 Pyrolysis Furnace	5-6
5.2.3 Aerosol Collection Equipment	5-8
5.3 Vaporization	5-13
5.3.1 Combustion Modeling	5-13
5.3.2 Vaporization Results and Modeling	5-43
5.4 Residual Ash Formation	5-105
5.4.1 Beneficiated Coal Performance in a Laminar Flow Reactor	5-105
5.4.2 Effect of Char Structure on Final Ash Distributions	5-111
5.4.3 Effect of Alkali Metals on Ash Coalescence	5-123
5.4.4 Effect of Ash Content on Final Ash Distribution	5-137
5.4.5 Continuum Modeling	5-139
5.5 Overall Summary and Conclusions	5-162
5.6 References	5-165
6. BEHAVIOR OF COAL INORGANIC SPECIES IN A LABORATORY SCALE PULVERIZED COAL COMBUSTOR (UA)	6-3
6.1 Laboratory Scale Combustor	6-3
6.1.1 Fuel Feed System	6-5
6.1.2 Air Feed System	6-6
6.1.3 Temperature Measurements	6-8
6.1.4 Gas Sampling System	6-8
6.1.5 Fly Ash Particle Sampling System	6-9

TABLE OF CONTENTS (Continued)

<u>Section No.</u>	<u>Page No.</u>
6.1.6 Fly Ash Analysis	6-12
6.2 General Experimental Procedure	6-13
6.3 Summary of Experiments	6-14
6.4 Coal Characterization - UA Supplemental Analysis	6-19
6.4.1 Loy Yang 2301 Supplemental Analysis	6-20
6.4.2 Gravimelt 7A Moisture Analysis	6-20
6.4.3 Analysis of Doped Coal Samples	6-22
6.5 Experimental Results	6-24
6.5.1 Base Case Burns - Phase I Coals	6-25
6.5.2 Modified Feed Rate/Temperature Profile Burns - Phase I Coals	6-56
6.5.3 Doped Coal Experiments - Phase I Coals	6-74
6.5.4 UA/PSIT Test Burns with In Situ Particle Distribution Measurement	6-84
6.5.5 Burns of Cleaned Coals	6-121
6.5.6 CCSEM Results	6-132
6.6 Analysis - Alkali Behavior	6-149
6.6.1 The Behavior of Alkali in a Coal Combustion Environment at Equilibrium	6-149
6.6.2 Mechanisms Governing Sodium Transformations During Pulverized Fuel Combustion	6-171
6.6.3 Sodium/Potassium Interactions	6-196
6.6.4 Dispersed Calcium Transformations	6-208
6.7 Mechanistic Model of Alkali Behavior	6-211
6.7.1 Interpretation of Size Segregated Ash Composition Data	6-211
6.7.2 Modelling Sodium Capture by Silicates During Pulverized Coal Combustion	6-227
6.7.3 Alkali Study: Conclusions and Recommendations	6-243
6.8 Analysis - Iron Behavior	6-246
6.8.1 Background	6-246
6.8.2 Iron-Silicate Interactions During Coal Combustion	6-246

TABLE OF CONTENTS (Continued)

<u>Section No.</u>	<u>Page No.</u>
6.9 Modeling of the Fate of Iron in Combustion-Derived Ash	6-259
6.9.1 Model Description	6-259
6.9.2 Model Parameters	6-261
6.9.3 Char Burnout	6-263
6.9.4 Glass Formation	6-265
6.9.5 Iron Oxide Formation	6-267
6.9.6 Particle Energy Balances	6-269
6.9.7 Model Results	6-270
6.9.8 Future Work	6-274
6.10 Variable Definitions	6-275
6.11 References	6-277
7. IDEALIZED COMBUSTION DETERMINATION OF ASH PARTICLE FORMATION AND SURFACE STICKINESS AND DEVELOPMENT OF AN ENGINEERING MODEL FOR THE PREDICTION OF ASH PARTICLE SIZE AND CHEMICAL COMPOSITION DISTRIBUTIONS (PSIT)	7-3
7.1 Background	7-4
7.2 Experimental Approach	7-6
7.2.1 Combustion and Particle Collection Systems	7-6
7.2.2 Particle Size and Composition Distribution Analysis	7-8
7.3 Experimental Results - Phase II Baseline Study	7-16
7.3.1 Phase II Illinois #6 and Illinois #6 SOAP	7-24
7.3.2 Loy Yang 1953	7-32
7.3.3 Eagle Butte/Kentucky #9 Blend	7-40
7.3.4 Gravimelt 7A (Kentucky #9)	7-61
7.3.5 Gravimelt 9C (Pittsburgh #8)	7-82
7.3.6 Submicron Fume Formation - Summary	7-93
7.4 Effect of Combustion Stoichiometry on Ash Formation: Reducing Conditions	7-98
7.5 In-situ Measurements of Ash Particle Size Distributions	7-103

TABLE OF CONTENTS (Continued)

<u>Section No.</u>	<u>Page No.</u>
7.5.1 Overview of Test Program	7-103
7.5.2 Test Results	7-105
7.5.3 Results as a Function of Combustion Temperature	7-113
7.6 PSIT/SECV Pilot Scale Combustion Testing	7-114
7.6.1 Background	7-114
7.6.2 Objectives and Description of Facilities	7-115
7.6.3 Coal Analysis	7-117
7.6.4 Results: Ash Particle Size and Composition	7-123
7.6.5 Comparison of Coals - Ash Particle Size Distributions	7-164
7.6.6 Deposition Results	7-168
7.6.7 Summary	7-178
7.7 Fundamental Ash Particle Stickiness Study	7-179
7.7.1 Extraneous Mineral Study	7-179
7.7.2 Stickiness Testing of Phase II Coals	7-191
7.7.3 Acknowledgment for Subsection 7.7.1	7-195
7.8 Trace Element Transformations	7-197
7.8.1 Coal and Ash Analysis	7-198
7.8.2 XAFS Analysis - Chromium	7-203
7.9 Development of an Engineering Model for Ash Particle Size and Composition	7-207
7.9.1 Background	7-207
7.9.2 Mineral Distribution Models	7-208
7.9.3 Simulation Results	7-215
7.9.4 Discussion of Results	7-230
7.9.5 Char Fragmentation Modeling	7-232
7.9.6 Conclusions and Significance	7-239
7.10 Phase II Conclusions - Tasks 7 and 8	7-239
7.10.1 Chemical Composition Distributions of Ash Particles	7-242

TABLE OF CONTENTS (Continued)

<u>Section No.</u>	<u>Page No.</u>
7.10.2 Effects of Combustion Scale	7-242
7.10.3 Effect of Reducing Conditions	7-243
7.10.4 Pilot Scale Testing at SECV	7-243
7.10.5 Clay Mineral Transformations	7-244
7.10.6 Stickiness of Ash From Beneficiated Coals	7-244
7.10.7 Trace Metal Transformations	7-245
7.10.8 Engineering Model to Predict Ash Particle Size and Composition Distributions	7-245
7.11 Section 7 References	7-246

List of Appendices

A - Inversion of MIT Cascade Impactor Data	A-1
B - MIT Computer Programs	B-1
C - Program Listings	C-1
D - UA Impactor Inversion Algorithm	D-1
E - Model Parameter Evaluation	E-1
F - Raw Data Listings - UA	F-1
G - Alkali Species Considered by the CET86 Equilibrium Program	G-1
H - CCSEM Data Listings - UA	H-1
I - CCSEM Plots - UA	I-1
J - Common Minerals in Coal and Coal Fly Ash	J-1
K - Input Parameters for Capture Model-518	K-1
L - CCSEM Data Summary for PSIT Samples	L-1
M - Phase II Ash CCSEM Summary - PSIT	M-1
N - PSIT Fortran Codes for Manipulation of CCSEM Data	N-1
O - CCSEM Classification Schemes - UKY and UNDEERC	O-1
P - Table of Contents - Phase I Final Report	P-1

LIST OF ILLUSTRATIONS

<u>Figure No.</u>		<u>Page No.</u>
1-1	Schematic diagram of ash formation process showing areas addressed by this program	1-2
1-2	Phase II program structure	2-4
3-1	Definition of coal mineralogy	3-4
3-2	Overview of SOAP cleaning process	3-6
3-3	Overview of "Gravimelt" chemical cleaning process	3-9
4-1	Volume percentage - ternary composition diagram for Ca-Fe-S phases in Beulah coal	4-180
4-2	Least squares analysis of the XANES from a Gravimelt-cleaned Kentucky #9 coal	4-181
4-3	Nepheline on filter	4-182
4-4	Na-Si-Al volume frequency for Nepheline	4-183
4-5	Montmorillonite on filter	4-184
4-6	Volume frequency for Montmorillonite	4-185
4-7	UA run 22 Beulah ash impactor #1	4-186
4-8	Volume frequency for UA run 22 Beulah Lignite impactor #1	4-187
4-9	UA runs 22 and 23 Beulah ash impactor #3	4-188
4-10	Volume frequency for UA run 22 Beulah Lignite impactor #3	4-189
4-11	Volume frequency for UA run 22 Beulah Lignite impactor #5	4-190
4-12	Volume frequency for UA run 22 Beulah Lignite impactor #7	4-191
4-13	Volume frequency for PSIT Beulah Lignite ash 7% oxygen, 1500 K	4-192
4-14	Volume frequency for PSIT Beulah Lignite ash 21% oxygen, 1500 K	4-193
4-15	UA run 23 Eagle Butte impactor #1	4-194
4-16	Volume frequency for UA run 23 Eagle Butte impactor #1	4-195
4-17	UA run 23 Eagle Butte impactor #5	4-196
4-18	Ca-Al-Mg volume frequency for PSIT/MIT-2 DTF run on Eagle Butte, 1750 K, 7% oxygen	4-197
4-19	PSIT ID #1g-a Kentucky #9, 7% O ₂ , 2350F	4-198
4-20	K-Si-Al volume frequency for PSIT #1g-a Kentucky #9, 0.2 g/min, 7% O ₂ , 2350F	4-199

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-21	UA run 24 Kentucky #9 impactor #1	4-200
4-22	Volume frequency for UA run 24 Kentucky #9 impactor #1	4-201
4-23	PSIT Kentucky #11 ash, 7% O ₂ , 1500 K	4-202
4-24	Volume frequency for PSIT Kentucky #11 ash, 7% oxygen, 1500 K	4-203
4-25	Volume frequency for UA run 27 Kentucky #11 impactor #1	4-204
4-26	Volume frequency for UA run 32 Upper Freeport	4-205
4-27	PSIT ID #if, Illinois #6, 7% O ₂ , 1500 K	4-206
4-28	Volume frequency for PSIT #if Illinois #6, 0.2 g/min, 7% O ₂ , 1500 K	4-207
4-29	UA run 21 Illinois #6 impactor #1	4-208
4-30	Volume frequency for UA run 21 Illinois #6 impactor #1	4-209
4-31	Volume frequency for PSIT San Miguel lignite ash, 7% oxygen, 1500 K, 3s RST	4-210
4-32	Volume frequency for PSIT San Miguel lignite ash, 21% oxygen, 1500 K, 3s RST	4-211
4-33	UA run 47B, Illinois #6, impactor #1 + cup	4-212
4-34	Volume frequency for UA run 47B, Illinois #6 Impactors 1 + cup	4-213
4-35	UA run 47B, Illinois #6, impactors 2 + 3 + 4	4-214
4-36	Volume frequency for UA run 47B, Illinois #6 impactors 2+3+4	4-215
4-37	UA run 47B, Illinois #6, impactors 5+6+7+8+AF	4-216
4-38	Volume frequency for UA run 47B, Illinois #6 impactors 5+6+7+8+AF	4-217
4-39	Volume frequency for UA run 47B, Illinois #6, impactors 2+3+4	4-218
4-40	UA run 51B, Illinois #6 SOAP, impactors 1+cup	4-219
4-41	Volume frequency for UA run 51B Illinois #6 SOAP impactors 1+cup	4-220
4-42	UA run 51B, Illinois #6 SOAP, impactors 2+3+4	4-221
4-43	UA run 51B, Illinois #6 SOAP, impactors 5+6+7+8+AF	4-222
4-44	UA run 48F, Beulah lignite, impactors 1+cup	4-223
4-45	UA run 48D, Beulah lignite, impactors 2+3+4	4-224
4-46	UA run 48B, Beulah lignite impactors 2+3+4	4-225

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-47	UA run 48B, Beulah lignite, impactors 5+6+7+8+AF	4-226
4-48	Volume frequency for UA run 48B, Beulah lignite impactors 5+6+7+8+AF	4-227
4-49	Volume frequency for PSIT/SECV Beulah lignite ash probe (combustion chamber)	4-228
4-50	Volume frequency for PSIT/SECV Beulah lignite ash probe (horizontal duct)	4-229
4-51	Volume frequency for PSIT/SECV Beulah lignite precipitator ash	4-230
4-52	PSIT/SECV Beulah lignite ash probe (combustion chamber)	4-231
4-53	UA runs 49B and 49H, Loy Yang 2301, impactors 5+6+7+8+AF	4-232
4-54	Volume frequency for UA runs 49B and 49H, Loy Yang 2301	4-233
4-55	UA run 49B, Loy Yang 2301	4-234
4-56	Volume frequency for UA run 49B, Loy Yang 2301	4-235
4-57	Volume frequency for UA run 49H Loy Yang 2301, impactors 5+6+7+8+AF	4-236
4-58	Loy Yang 2301	4-237
4-59	Volume frequency for UA run 49H, Loy Yang 2301, impactors 2+3+4	4-238
4-60	UA run 50D, Loy Yang 1953, impactors 2+3+4	4-239
4-61	UA run 50D, Loy Yang 1953, impactors 5+6+7+8+AF	4-240
4-62	Volume frequency for UA run 50D, Loy Yang 1953, impactors 5+6+7+8+AF	4-241
4-63	Volume frequency for PSIT/SECV test #1	4-242
4-64	PSIT/SECV Loy Yang test #4, Mg-Al-Ca	4-243
4-65	PSIT/SECV Loy Yang, Fe-Mg-Al	4-244
4-66	PSIT/SECV Loy Yang 1953, Na-S-Cl	4-245
4-67	Na-Si-Al volume frequency for PSIT/SECV test #1 on untreated Loy Yang ash probe (ring 7) and Na-Si-Al col. frequency for PSIT/SECV test #4 on untreated Loy Yang ash probe (horizontal duct)	4-246
4-68	Ion-exchanged Beulah coal: Ca-Al-Si ash	4-247

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-69	Volume frequency for ion-exchanged Beulah ash	4-248
4-70	K-Al-Si Beulah ash (ion-exchanged sample)	4-249
4-71	Volume frequency for Beulah ash, ion-exchanged sample	4-250
4-72	Volume frequency for Beulah ash, ion-exchanged sample	4-251
4-73	Volume frequency for Beulah ash, ion-exchanged sample	4-252
4-74	Energy dispersive X-ray (EDX) spectrum of the ceramic tube, PSIT/SECV tests	4-253
4-75	SEM micrograph for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606)	4-254
4-76	SEM X-ray maps for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606)	4-254
4-77	SEM micrograph for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606)	4-255
4-78	SEM X-ray maps for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606)	4-255
4-79	SEM micrograph for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606)	4-256
4-80	SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607)	4-257
4-81	SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607)	4-257
4-82	SEM micrograph for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607)	4-258
4-83	SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607)	4-258
4-84	SEM micrograph for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608)	4-259

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-85	SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608)	4-259
4-86	SEM micrograph for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608)	4-260
4-87	SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608)	4-260
4-88	Energy Dispersive X-ray (EDX) spectrum of region 1 in Figure 4-86	4-261
4-89	SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608)	4-261
4-90	SEM micrograph for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609)	4-262
4-91	SEM X-ray maps for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609)	4-262
4-92	SEM micrograph for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609)	4-263
4-93	SEM X-ray maps for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609)	4-263
4-94	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-264
4-95	SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-264
4-96	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-265
4-97	SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-265
4-98	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-266

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-99	SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-266
4-100	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-267
4-101	Energy dispersive X-ray (EDX) spectra of different regions marked in Figure 4-100	4-268
4-102	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-269
4-103	SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-269
4-104	SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-270
4-105	SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610)	4-270
4-106	Mössbauer spectra obtained from ash probe samples taken during PSIT/SECV tests	4-271
4-107	XANES for Ca standard compounds	4-272
4-108	EXAFS RSF for Ca standard compounds	4-273
4-109	EXAFS RSF for Ca standard compounds	4-274
4-110	XANES of calcium acetate treated sucrose char and of samples prepared from it in a DTF	4-572
4-111	Ca RSF derived from EXAFS of sucrose chars with Ca (CH ₃ CO)) ₂ and SiO ₂ formed in MIT drop tube furnace at wall temperature with 20% oxygen partial pressure	4-276
4-112	Ca XANES from suite of model chars prepared by MIT group	4-277
4-113	RSF of two model ashes from MIT	4-278
4-114	Typical Ca XANES for impactor 1 and higher impactor number ash samples	4-279
4-115	RSF of the Beulah and Eagle Butte impactor 1 as samples	4-280

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
4-116	Ca XANES for ash from Beulah parent and ion exchanged coal	4-281
4-117	XANES of potassium standard compounds	4-282
4-118	Comparison of the XANES of K_2SO_4 to that of the ion-exchanged ash samples and an MIT sample	4-283
4-119	RSF of K_2SO_4 compared to that of an ion-exchanged ash and an MIT sample	4-284
4-120	Potassium XANES spectra of a series of MIT samples	4-285
4-121	In-situ K-XANES of KOH-Kaolinite mixture at different temperatures	4-286
4-122	Ca XANES of in-situ reaction between $Ca(OH)_2$ and kaolinite	4-287
4-123	High temperature in-situ Fe XANES of ash	4-288
4-124	Radial structure function of high temperature in-situ Fe EXAFS	4-289
4-125	As K-edge XANES spectra of Upper Freeport coal fractions and ash	4-290
5.2-1	MIT laminar entrained flow reactor	5-5
5.2-2	Temperature profiles in the MIT laminar entrained flow reactor	5-7
5.2-3	Pyrolysis furnace used for synthetic char preparation	5-8
5.2-4	Temperature profiles in the pyrolysis furnace	5-9
5.2-5	Aerosol collection systems	5-10
5.2-6	Cascade impactor	5-11
5.2-7	Removal efficiency versus particle size for each stage of the cascade impactor	5-12
5.2-8	Cumulative penetration curve for first six impactor stages	5-12
5.3-1	Temperature calculation algorithm	5-28
5.3-2	Effect of oxygen dissociation on thermal conductivity	5-34
5.3.3	Effect of the O_2/C ratio on the predicted particle temperature	5-37
5.3-4	Temperature versus oxygen concentration	5-42
5.3.5	Scanning electron micrographs and particle size distribution by laser diffraction of the 90 to 106 μm sucrose/50% carbon block char	5-48

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
5.3.6	Scanning electron micrographs of four cross sections of 90 to 106 μm sucrose/carbon black char particles doped with 4 wt%, 1 to 5 μm hydrothermal pyrite particles	5-50
5.3-7	Vaporization model	5-59
5.3.8	Calculated average calcium vapor pressure at the char surface during burnout compared to several equilibrium calcium vapor pressure curves	5-74
5.3-9	Comparison of the average calcium vapor pressure at the char surface calculated from the data to those calculated from the model	5-77
5.3-10	Comparison of current calcium vaporization results to the previous results of Quann and Sarofim (1982)	5-79
5.3-11	Calculated average silicon vapor pressure at the char surface during burnout compared to several equilibrium silicon vapor pressure curves assuming silicon dioxide is the condensed phase	5-80
5.3-12	Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from the silicon dioxide model	5-85
5.3-13	Calculated average silicon vapor pressure at the char surface during burnout compared to several equilibrium silicon vapor pressure curves assuming silicon carbide is the condensed phase	5-87
5.3-14	Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from the silicon carbide model	5-88
5.3-15	Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from three different models	5-90
5.3-16	Comparison of current silicon vaporization results to previous results	5-91
5.3-17	Calculated average iron vapor pressure at the char surface during burnout compared to equilibrium iron vapor pressure curves assuming iron oxide is the condensed phase	5-93

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
5.3-18	Fe-S phase diagram	5-95
5.3-19	Calculated average iron vapor pressure at the char surface during burnout compared to the equilibrium iron vapor pressure curve assuming iron is the condensed phase	5-98
5.3-20	Comparison of average iron vapor pressures at the char surface calculated from the data to those calculated from the iron model	5-99
5.3-21	Calculated average iron vapor pressure at the char surface during burnout compared to several equilibrium iron vapor pressure curves assuming iron sulfide is the condensed phase	5-100
5.3-22	Comparison of average iron vapor pressure at the char surface calculated from the data to those calculated from the iron sulfide model	5-102
5.3-23	Comparison of current iron vaporization results to the previous results of Quann (1982)	5-103
5.4-1	Inverted ash mass distributions of Gravimelt 7A (Kentucky #9) as measured by cascade impactor runs at different conditions 63/75 μm coal sample	5-106
5.4-2	Inverted ash mass distributions of Gravimelt 9C (Pittsburgh 8) as measured by cascade impactor runs at different conditions 63/74 μm coal sample	5-106
5.4-3	Inverted ash mass distributions of Loy Yang 1953 as measured by cascade impactor runs at different conditions 63/75 μm coal sample	5-107
5.4-4	Ash mass distributions of 70/30 Blend (EB/Ky 9) by the cascade impactor runs at different conditions	5-107
5.4-5	Cross-sectional Images of Chars from Gravimelt 7A and Kentucky No. 9 bituminous coal	5-110
5.4-6	Schematic diagram of experimental procedure for studies on the effect of the char burnout mechanism on residual ash formation	5-112
5.4-7	Cross-sectioned images of char particles at various preparation stages	5-113

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
5.4-8	The density distribution and mineral content variation of the air-classified, and size-classified Kentucky No. 9 bituminous coal	5-114
5.4-9	Pore size distributions of the pyrolyzed char particles	5-116
5.4-10	The final ash mass distributions obtained from the two sample chars	5-117
5.4-11	Snapshots of two-dimensional char with a macroporosity of 0.3 represented in 50 x 50 matrix with random pores and after 4, 8, and 12 combinations of adjacent pores	5-120
5.4-12	Ash mass distributions obtained from ash formation simulation for the two chars in Figure 5.4-11	5-121
5.4-13	Snapshots of 50 x 50 square lattice configurations constructed by following the scheme	5-122
5.4-14	Schematic diagram of time-temperature history of silica growth	5-126
5.4-15	Pore size distributions of sucrose/carbon black char obtained from mercury porosimetry	5-128
5.4-16	An example of the time-temperature history of a char particle	5-129
5.4-17	Fusion curves of alkali and alkaline-earth silicates and the viscosity change of silica with alkali metal addition	5-130
5.4-18	Typical ash particles collected from the combustion of sample BA and sample KL	5-131
5.4-19	Cumulative particle size distributions of the <i>primary</i> particles and volume mean particle size change with the composition	5-134
5.4-20	Ash mass distributions from cascade impactor runs	5-135
5.4-21	Comparison of ash size distributions of Kentucky No. 9 coal samples	5-138
5.4-22	Illustration of the formation of a fly ash particle	5-143
5.4-23	Illustration of the coalescence length scale for spherical char configuration	5-149

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
5.4-24	Growth of average surface ash size rescaled with mineral inclusion size (r_{ash}/r_m) with the reaction depth z and the depth rescaled with the separation length (z/L_g)	5-154
5.4-25	Final ash size distributions	5-155
5.4-26	Growth of the average surface ash radius obtained from the computer simulation of a typical bituminous coal	5-156
5.4-27	Surface ash PSD's obtained from the simulation of a typical bituminous coal of 8 vol% mineral content	5-158
5.4-28	Growth of surface ash with conversion of a non-porous char	5-159
5.4-29	Correlation between the ash growth number and the mass mean radii of separated and surface ash	5-160
5.4-30	Ash mass distributions from simulations in spherical configuration	5-161
6.1-1	UA laboratory scale combustor	6-4
6.1-2	Coal feeder	6-5
6.1-3	Plenum section of furnace	6-6
6.1-4	Air feed system	6-7
6.1-5	Coal-air mixing section	6-7
6.1-6	Gas sampling system	6-9
6.1-7	Particle sampling system	6-10
6.1-8	Particle sampling probe	6-10
6.1-9	Impactor configurations	6-12
6.4-1	Moisture analysis of UA Gravimelt 7A	6-20
6.5-1	Temperature profile for burn 13, Baulah	6-26
6.5-2	Temperature profile for burn 14, Baulah	6-26
6.5-3	Fraction oxide plot for burn 13	6-27
6.5-4	Fraction oxide plot for burn 14	6-28
6.5-5	Ash concentration for burn 13	6-29

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>
6.5-6	6-29
6.5-7	6-31
6.5-8	6-31
6.5-9	6-32
6.5-10	6-33
6.5-11	6-34
6.5-12	6-34
6.5-13	6-36
6.5-14	6-36
6.5-15	6-37
6.5-16	6-38
6.5-17	6-39
6.5-18	6-39
6.5-19	6-40
6.5-20	6-40
6.5-21	6-41
6.5-22	6-42
6.5-23	6-43
6.5-24	6-43
6.5-25	6-45
6.5-26	6-45
6.5-27	6-46
6.5-28	6-47
6.5-29	6-48
6.5-30	6-48
6.5-31	6-50
6.5-32	6-51
6.5-33	6-51

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>	
6.5-34	Temperature profile for burn 31, Loy Yang 2301	6-52
6.5-35	Fraction oxide plot for burn 30.	6-53
6.5-36	Fraction oxide plot for burn 31.	6-54
6.5-37	Ash concentration for burn 30.	6-55
6.5-38	Ash concentration for burn 31.	6-55
6.5-39	Temperature profile for burn 34, Upper Freeport	6-57
6-5-40	Temperature profile for burn 35, Upper Freeport	6-57
6.5-41	Fraction oxide plot for burn 34.	6-58
6.5-42	Fraction oxide plot for burn 35.	6-59
6.5-43	Ash concentration for burn 34.	6-60
6.5-44	Ash concentration for burn 35.	6-60
6.5-45	Temperature profiles for burn 36, Kentucky #9.	6-62
6.5-46	Fraction oxides for burn 36 high temperature.	6-62
6.5-47	Fraction oxides for burn 36 low temperature.	6-63
6.5-48	Ash concentration for burn 36 high temperature.	6-63
6.5-49	Ash concentration for burn 36 low temperature.	6-64
6.5-50	Temperature profiles for burn 37, Kentucky #11	6-65
6.5-51	Fraction oxides for burn 37 high temperature.	6-65
6.5-52	Fraction oxides for burn 37 low temperature.	6-66
6.5-53	Ash concentration for burn 37 high temperature.	6-66
6.5-54	Ash concentration for burn 37 low temperature.	6-67
6.5-55	Temperature profiles for burn 38, Beulah	6-68
6.5-56	Fraction oxides for burn 38 high temperature.	6-68
6.5-57	Fraction oxides for burn 38 low temperature.	6-69
6.5-58	Ash concentration for burn 38 high temperature.	6-70
6.5-59	Ash concentration for burn 38 low temperature.	6-70
6.5-60	Temperature profiles for burn 39, Loy Yang 2301	6-71
6.5-61	Fraction oxides for burn 39 high temperature.	6-71

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>
6.5-62	6-72
6.5-63	6-73
6.5-64	6-73
6.5-65	6-74
6.5-66	6-75
6.5-67	6-75
6.5-68	6-76
6.5-69	6-76
6.5-70	6-78
6.5-71	6-78
6.5-72	6-79
6.5-73	6-80
6.5-74	6-80
6.5-75	6-82
6.5-76	6-82
6.5-77	6-83
6.5-78	6-83
6.5-79	6-84
6.5-80	6-87
6.5-81	6-87
6.5-82	6-88
6.5-83	6-89
6.5-84	6-89
6.5-85	6-90
6.5-86	6-90
6.5-87	6-91
6.5-88	6-92

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>
6.5-89 Ash concentration for 2.4 kg/hr feed rate	6-93
6.5-90 Mass distributions for burn 47.	6-93
6.5-91 Area distribution for burn 47.	6-94
6.5-92 Number distributions for burn 47.	6-94
6.5-93 Impactor and PCSV-P psd for burn 47.	6-95
6.5-94 Impactor and PCSV-P for burn 47.	6-96
6.5-95 Temperature profiles for burn 48, Beulah	6-97
6.5-96 Fraction oxide for 1.65 kg/hr feed rate.	6-97
6.5-97 Fraction oxide for 2.8 kg/hr feed rate.	6-98
6.5-98 Ash concentration for 1.65 kg/hr feed rate.	6-99
6.5-99 Ash concentration for 2.8 kg/hr feed rate.	6-99
6.5-100 Fraction oxide for burn 48 port 5.	6-100
6.5-101 Ash concentration for burn 48 port 5.	6-100
6.5-102 Mass distribution for burn 48 low feed rate.	6-101
6.5-103 Mass distribution for burn 48 high feed rate.	6-102
6.5-104 Mass distributions for burn 48.	6-102
6.5-105 Area distributions for burn 58.	6-103
6.5-106 Number distributions for burn 48.	6-103
6.5-107 Cumulative mass versus cutoff diameter for burn 48.	6-104
6.5-108 Impactor and PCSV-P psd for burn 48, differential	6-105
6.5-109 Impactor and PCSV-P psd for burn 48, cumulative	6-105
6.5-110 Impactor and PCSV-P psd for burn 48, differential, high feed rate	6-106
6.5-111 Impactor and PCSV-P psd for burn 48, cumulative, high feed rate	6-106
6.5-112 Temperature profile for burn 49, Loy Yang 2301	6-107
6.5-113 Fraction oxide for 1.8 kg/hr feed rate.	6-108
6.5-114 Fraction oxide for 2.8 kg/hr feed rate.	6-108
6.5-115 Ash concentration for 1.8 kg/hr feed rate.	6-109
6.5-116 Ash concentration for 2.8 kg/hr feed rate.	6-109

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
6.5-117	Mass distribution for burn 49 low feed rate.	6-110
6.5-118	Mass distribution for burn 49 high feed rate.	6-111
6.5-119	Mass distributions for burn 49	6-111
6.5-120	Area distributions for burn 49.	6-112
6.5-121	Number distributions for burn 49.	6-112
6.5-122	Impactor and PCSV-P psd for burn 49, differential	6-113
6.5-123	Impactor and PCSV-P psd for burn 49, cumulative	6-113
6.5-124	Impactor and PCSV-P psd for burn 49, differential, high feed rate	6-114
6.5-125	Impactor and PCSV-P psd for burn 49, cumulative, high feed rate	6-114
6.5-126	Imp without 8+AF and PCSV-P psd for burn 49, differential	6-115
6.5-127	Imp without 8+AF and PCSV-P psd for burn 49, cumulative	6-115
6.5-128	Temperature profile for burn 50, Loy Yang 1953	6-116
6.5-129	Fraction oxide for 2.5 kg/hr feed rate.	6-117
6.5-130	Ash concentration for 2.5 kg/hr feed rate.	6-117
6.5-131	Sodium cumulative fraction for burn 49 and 50.	6-118
6.5-132	Mass distribution for burn 50.	6-119
6.5-133	Area distribution for burn 50.	6-119
6.5-134	Number distribution for burn 50.	6-120
6.5-135	Impactor and PCSV-P for psd burn 50, differential	6-120
6.5-136	Impactor and PCSV-P psd for burn 50, cumulative	6-121
6.5-137	Temperature profile for burn 51, Illinois #6 SOAP	6-123
6.5-138	Temperature profile for burn 54, Illinois #6 SOAP	6-123
6.5-139	Fraction oxide for burn 51.	6-124
6.5-140	Fraction oxide for burn 54.	6-124
6.5-141	Ash concentration for burn 51.	6-125
6.5-142	Ash concentration for burn 54.	6-125
6.5-143	Temperature profile for burn 52, Gravimelt 7A	6-126
6.5-144	Temperature profile for burn 53, Gravimelt 7A	6-127

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>
6.5-145	Fraction oxide for burn 52 at 1.9 kg/hr. 6-127
6.5-146	Fraction oxide for burn 53 at 1.8 kg/hr. 6-128
6.5-147	Ash concentration for burn 52 6-129
6.5-148	Ash concentration for burn 53. 6-129
6.5-149	Uncorrected temperature profile for run 59; Kentucky 9 - Eagle Butte Blend 6-130
6.5-150	Uncorrected temperature profile for run 60; Kentucky 9 - Eagle Butte Blend 6-130
6.5-151	Fraction oxide versus impactor stage for run 59; Kentucky 9 - Eagle Butte Blend 6-131
6.5-152	Fraction oxide versus impactor stage for run 60; Kentucky 9 - Eagle Butte Blend 6-131
6.5-153	Base of typical 3D plot 6-133
6.5-154	Al versus Si Illinois No. 6 impactor 1 6-135
6.5-155	Ca versus Si Illinois No. 6 impactor 1 6-136
6.5-156	Fe versus Si Illinois No. 6 impactor 1 6-137
6.5-157	Na versus Si Illinois No. 6 impactor 1 6-137
6.5-158	K versus Si Illinois No. 6 impactor 1 6-138
6.5-159	Al versus Si Beulah Lignite impactor 1 6-139
6.5-160	Al versus Si Beulah Lignite Impactor 3 6-140
6.5-161	Al versus Si Beulah Lignite Impactor 5 6-140
6.5-162	Al versus Si Beulah Lignite Impactor 7 6-141
6.5-163	Ca versus Si Beulah Lignite Impactor 1 6-142
6.5-164	Ca versus Si Beulah Lignite Impactor 3 6-142
6.5-165	Ca versus Si Beulah Lignite Impactor 5 6-143
6.5-166	Ca Versus Si Beulah Lignite Impactor 7 6-143
6.5-167	Na versus Si Eagle Butte Impactor 1 6-145
6.5-168	Na versus Si for Eagle Butte Impactor 5 6-145

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
6.5-169	Na versus Si Beulah Lignite Impactor 1	6-146
6.5-170	Na versus Si Beulah Lignite Impactor 3	6-146
6.5-171	Na versus Si Beulah Lignite Impactor 5	6-147
6.5-172	Na versus Si Beulah Lignite Impactor 7	6-147
6.5-173	Loy Yang 2301 + kaolinite, Al+Si+Na > 80%, dp > 10 μ m	6-148
6.5-174	Loy Yang 2301 + kaolinite, Al+Si+Na > 80%, dp < 10 μ m	6-148
6.6-1	Results for sodium in Upper Freeport	6-151
6.6-2	Results for potassium in Upper Freeport	6-151
6.6-3	Results for sodium in Kentucky No. 11	6-152
6.6-4	Results for potassium in Kentucky No. 11.	6-152
6.6-5	Results for sodium in Kentucky No. 9.	6-153
6.6-6	Results for potassium in Kentucky No. 9.	6-153
6.6-7	Results for sodium in Illinois No. 6.	6-154
6.6-8	Results for potassium in Illinois No. 6.	6-154
6.6-9	Results for sodium in Beulah Lignite.	6-155
6.6-10	Results for potassium in Beulah Lignite.	6-155
6.6-11	Results for sodium in Eagle Butte.	6-156
6.6-12	Results for potassium in Eagle Butte.	6-156
6.6-13	Results for sodium in Loy Yang 2301.	6-157
6.6-14	Results for potassium in Loy Yang 2301.	6-157
6.6-15	Results for sodium in Loy Yang 1953.	6-158
6.6-16	Results for potassium in Loy Yang 1953.	6-158
6.6-17	Sodium species in Illinois No. 6 SOAP.	6-161
6.6-18	Potassium species in Illinois #6 SOAP.	6-162
6.6-19	Sodium species in Kentucky No. 9 7A.	6-162
6.6-20	Potassium species in Kentucky No. 9 7A.	6-163
6.6-21	Sodium species in Kentucky #11 + NaAc.	6-163
6.6-22	Potassium species in Kent #11 + NaAc.	6-164

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>	<u>Page No.</u>
6.6-23 Sodium in Loy Yang 2301 + kaolinite.	6-164
6.6-24 Potassium in Loy Yang 2301 + kaolinite.	6-165
6.6-25 Evolution of sodium with K, Cl, and S	6-167
6.6-26 Effect of potassium on sodium.	6-168
6.6-27 Evolution of K with Na, Cl, and S.	6-169
6.6-28 Effect of sodium on potassium	6-169
6.6-29 Effect of sodium on potassium, low aluminosilicates	6-170
6.6-30 Arrhenius plot for heating rate experiment	6-177
6.6-31 Cumulative fraction for sodium burn 39.	6-182
6.6-32 Cumulative fraction for potassium burn 39.	6-182
6.6-33 Cumulative fraction for sodium burn 41.	6-184
6.6-34 Cumulative fraction for potassium burn 41.	6-184
6.6-35 Cumulative fraction of sodium for burn 38.	6-185
6.6-36 Cumulative fraction for sodium burn 42.	6-187
6.6-37 Cumulative fraction for potassium burn 42.	6-187
6.6-38 Burn 42 sample A silicon.	6-188
6.6-39 Burn 42 sample B silicon.	6-188
6.6-40 Burn 42 sample A sodium.	6-189
6.6-41 Burn 42 sample B sodium.	6-189
6.6-42 Burn 42 sample A potassium.	6-190
6.6-43 Burn 42 sample B potassium.	6-190
6.6-44 Sodium f_{8A} versus Na/AlSi.	6-192
6.6-45 m_{Na}/M versus $1/d_p^2$ for Beulah Lignite.	6-194
6.6-46 Potassium f_{8A} versus K/AlSi.	6-198
6.6-47 K versus Na in small sizes.	6-199
6.6-48 Potassium f_{8A} versus chlorine content	6-200
6.6-49 Potassium f_{8A} for Kentucky No. 11.	6-202
6.6-50 Reactor #1 for potassium displacement experiments.	6-203

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
6.6-51	Ratio of alkali to Al + Si for KaOK.	6-204
6.6-52	Configuration #3 for illite experiments	6-205
6.6-53	Results of illite experiments.	6-207
6.7-1	$\Theta + f_9$ versus f_{8A} for Na.	6-216
6.7-2	$\Theta + f_9$ versus f_{8A} for K.	6-217
6.7-3	Model results for sample 42A sodium.	6-218
6.7-4	Solubility results for sample 42A sodium.	6-219
6.7-5	Model results for sample 42B sodium.	6-219
6.7-6	Solubility results for sample 42B sodium.	6-220
6.7-7	Model results for sample 42A potassium.	6-221
6.7-8	Solubility results for sample 42A potassium.	6-221
6.7-9	Model results for sample 42B potassium.	6-222
6.7-10	Solubility results for sample 42B potassium.	6-222
6.7-11	Captured Na versus Si distribution plates 2-Af.	6-223
6.7-12	Captured Na versus Si distribution plates 1-Af.	6-223
6.7-13	Model results for burn 38 sodium.	6-224
6.7-14	Model results for burn 38 potassium.	6-224
6.7-15	Model results for burn 40 sodium.	6-225
6.7-16	Model results for burn 40 potassium.	6-225
6.7-17	$\Theta + f_9$ for K and Na for six coals.	6-226
6.7-18	Fraction of condensable sodium measured in the cascade impactor as a function of measured peak temperature for six separate coals	6-228
6.7-19	Schematic diagram of sodium diffusion through a shrinking char particle	6-229
6.7-20	NaCl release	6-236
6.7-21	$\text{Na}_{(\text{org})}$ release	6-236
6.7-22	Capture model and impactor data for Beulah lignite	6-237
6.7-23	Capture model and impactor data for Eagle Butte	6-237

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
6.7-24	Capture model and impactor data for Loy Yang 2301	6-238
6.7-25	Capture model and impactor data for Kentucky No. 11	6-239
6.7-26	Capture model and impactor data for Illinois No. 6	6-240
6.7-27	Capture model and impactor data for Kentucky No. 9.	6-240
6.8-1	Proposed iron-silicate interactions.	6-247
6.8-2	XRD spectrum from Illinois #6 ash trap sample.	6-249
6.8-3	XRD spectrum from Illinois #6 ash trap sample.	6-250
6.8-4	EDX spectrum of large glassy particles.	6-252
6.8-5	EDX spectrum of plate-like particles.	6-252
6.8-6	EDX spectrum of large beam-stable particles.	6-253
6.8-7	EDX spectrum of needle-like particles in composite particles.	6-253
6.8-8	EDX of glassy matrix of composite particles.	6-254
6.8-9	Ash agglomeration from Beulah Lignite, plate 1.	6-255
6.8-10	Fe map, agglomerate in Figure 6.8-9.	6-255
6.8-11	Si map, agglomerate in Figure 6.8-9.	6-256
6.8-12	Agglomerate in Figure 6.8-9 under low magnification.	6-256
6.8-13	Ash agglomerate from Illinois #6, plate 1.	6-257
6.8-14	Fe map agglomerate in Figure 6.8-13.	6-257
6.8-15	Si map, agglomerate in Figure 6.8-13.	6-258
6.8-16	The agglomerate from Figure 6.8-13 under lower magnification.	6-258
6.9-1	Pathway for ash movement to surface.	6-260
6.9-2	Iron partitioning pathways.	6-260
6.9-3	High probability of contact.	6-266
6.9-4	Low probability of contact.	6-266
6.9-5	Oxidation pathways for inherent and extraneous pyrite.	6-268
6.9-6	Comparison of predicted and measured fraction iron as glass.	6-271
6.9-7	Predicted temperature profiles.	6-272
6.9-8	Iron partitioning as a function of residence time.	6-273

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
6.9-9	Char behavior as a function of residence time.	6-273
6.9-10	Fraction iron in slag-causing phases as a function of time	6-274
7.1-1	Mass probability distribution of base/acid ratios for distribution of ash particle chemical compositions measured in a bench-scale combustion experiment at PSIT	7-5
7.2-1	PSIT laboratory reactor	7-6
7.2-2	Schematic diagram of feeder designed to feed 70% < 200 mesh grind uniformly	7-7
7.2-3	Particle stickiness (adhesion efficiency) probe	7-9
7.2-4	Furnace - probe temperatures	7-9
7.2-5	Comparison of calculated CCSEM particle size distributions	7-13
7.2-6	Calculated d_{50} for PCSC Mark III cascade impactor	7-14
7.2-7	Schematic diagram of PCSV-P operating principle	7-15
7.3-1	CCSEM mineral size distributions for three Phase II beneficiated coals and Illinois #6 parent coal	7-16
7.3-2	CCSEM mineral size distributions for Phase II blend, blend parent coals, and Loy Yang 1953 coal	7-17
7.3-3	CCSEM mineral size distributions for Phase I low-rank coals	7-18
7.3-4	CCSEM mineral size distributions for Phase I bituminous coals	7-19
7.3-5	Coal particle size distribution for selected Phase I coals, measured with Malvern 2600C Particle Sizer	7-20
7.3-6	Coal particle size distribution for selected Phase I coals, measured via Malvern at EER	7-20
7.3-7	Coal particle size distribution for Phase I coals by screen analysis	7-21
7.3-8	CCSEM ash particle size distribution for low-ash Phase II coals	7-21
7.3-9	CCSEM ash particle size distributions for low-rank Phase I coals	7-22
7.3-10	CCSEM ash particle size distributions for bituminous Phase I coals	7-22

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.3-11	CCSEM mineral size distributions for Phase I and Phase II Illinois #6 bituminous coals	7-26
7.3-12	CCSEM mineral size distributions for PSIT Illinois #6 SOAP, ABB/CE SOAP, and Phase I and Phase II Illinois #6 bituminous coals	7-28
7.3-13	Mineral and ash size distributions for Illinois #6 SOAP	7-29
7.3-14	Fe-Al-Si ternary diagrams for Illinois 6 SOAP with $0.2 \leq dp < 80 \mu\text{m}$, $\text{Fe} + \text{Al} + \text{Si} \geq 80 \text{ atom\%}$	7-31
7.3-15	K-Al-Si ternary diagrams for Illinois 6 SOAP ash with $0.2 \leq dp < 80 \mu\text{m}$, $\text{K} + \text{Al} + \text{Si} \geq 80 \text{ atom\%}$	7-32
7.3-16	Ca-Al-Si ternary diagrams for Illinois 6 SOAP ash with $0.2 \leq dp < 80 \mu\text{m}$, $\text{Ca} + \text{Al} + \text{Si} \geq 80 \text{ atom\%}$	7-33
7.3-17	CCSEM mineral and ash particle size distributions for PSIT/UA Loy Yang 1953, SECV Loy Yang 1953, UA combustion ash (impactor stage 1), and PSIT/SECV combustion ash	7-37
7.3-18	Cascade impactor results, Loy Yang 1953, 7% oxygen	7-38
7.3-19	Cascade impactor results, Loy Yang 1953, 21% oxygen, 1700 K	7-38
7.3-20	Cascade impactor PSD, Loy Yang 2301, 21% O ₂ , 1500 K	7-39
7.3-21	CCSEM mineral size distributions for Phase II Eagle Butte, Phase I Eagle Butte, Phase II Kentucky #9, and Phase I Kentucky #9 coals	7-42
7.3-22	CCSEM mineral size distributions for Phase II Eagle Butte, Phase II Kentucky #9, and Phase II 70/30 Eagle Butte/Kentucky #9 blend	7-44
7.3-23	Cumulative ash volume distributions obtained by Malvern analysis	7-44
7.3-24	Comparison of measured Eagle Butte ash particle size distribution (Malvern analysis) and a distribution calculated assuming that one ash particle is generated per coal particle	7-45
7.3-25	CCSEM particle size distributions for ash generated from combustion of Phase II Eagle Butte, Phase II Kentucky #9, and 70/30 Eagle Butte/Kentucky #9 blend	7-46

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.3-26	CCSEM particle size distributions for Phase II Eagle Butte minerals and combustion generated ash produced in 7% oxygen at 1700 K	7-47
7.3-27	Ca-Al-Si ternary diagram for ash generated during combustion of Phase I Eagle Butte coal in 7% oxygen	7-49
7.3-28	CCSEM particle size distributions for Phase II Kentucky #9 minerals and combustion generated ash produced in 7% oxygen at 1700 K	7-50
7.3-29	Fe-Al-Si ternary diagram for ash generated during combustion of Phase I Kentucky #9 coal in 7% oxygen	7-52
7.3-30	CCSEM particle size distributions for blend minerals and combustion generated ash produced in 7% oxygen at 1700 K	7-53
7.3-31	(Alkali+alkaline earth) - Al - Si ternary diagrams for blend coal ash	7-55
7.3-32	Ternary diagram ((Ca + Na + K + Mg) - (Si + Al) - S) of all ash particles containing sulfur produced by the combustion of the blended coal at 1700 K, 7% O ₂	7-57
7.3-33	Ternary diagrams (Ca - Al - Si) of all ash particles containing sulfur produced by the combustion of the blended coal at 1700 K, 7% O ₂	7-59
7.3-34	Ternary diagrams (Ca - Al - Si) of all ash particles containing sulfur produced by the combustion of the blended coal at 1700 K, 7% O ₂ , and showing the composition of particles containing different amounts of sulfur	7-60
7.3-35	CCSEM mineral and ash size distributions for Gravimelt 7A and parent Kentucky #9	7-66
7.3-36	CCSEM quartz mineral and silica ash particle size distributions for Gravimelt 7A	7-67
7.3-37	Illite mineral and ash particle size distributions by CCSEM	7-68
7.3-38	K-Al-Si Ternary composition diagram for Gravimelt 7A, all particles 0.5 to 80 μ m, $\geq$ 80 atom percent K + Al + Si	7-69

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.3-39	K-Al-Si Ternary composition diagram for Gravimelt 7A illite-type particles	7-70
7.3-40	K-Al-Si Ternary composition diagram for Gravimelt 7A kaolinite-type particles	7-71
7.3-41	Size distributions for Gravimelt 7A mineral and ash particles which do not correspond to a crystalline mineral category	7-72
7.3-42	Gravimelt 7A Fe-Al-Si Ternary composition diagram	7-74
7.3-43	Gravimelt 7A Ca-Al-Si Ternary composition diagram	7-75
7.3-44	Na Ternary composition diagrams for Gravimelt 7A coal minerals	7-77
7.3-45	Na-Al-Si Ternary diagrams for Gravimelt 7A combustion-generated ash	7-78
7.3-46	Ternary diagrams for Gravimelt 7A titanium minerals and ash particles	7-79
7.3-47	Cascade impactor size distribution for combustion-generated ash	7-81
7.3-48	CCSEM mineral analysis of Gravimelt 9C (Pittsburgh #8), showing all particles containing greater than 60 atom percent K+Cl+S on an oxygen-free basis	7-85
7.3-49	Mineral and ash size distributions for Gravimelt 9C	7-87
7.3-50	CCSEM quartz mineral and ash size distributions for Gravimelt 9C	7-88
7.3-51	CCSEM Ti-Al-Si ternary for Gravimelt 9C, showing all minerals containing ≥ 50 atom% Ti+Al+Si	7-90
7.3-52	CCSEM Ti-Al-Si ternary for ash particles generated during combustion of Gravimelt 9C ($< 90 \mu\text{m}$), 1500°C 7% O_2	7-91
7.3-53	CCSEM Ti-Al-Si ternary for ash particles generated during combustion of Gravimelt 9C ($< 90 \mu\text{m}$), 1500°C 7% O_2	7-92

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.3-54	Cascade impactor mass distribution obtained from combustion of Gravimelt 9C at a gas temperature of 1700 K	7-93
7.4-1	CCSEM ash particle size distributions generated by combustion of Phase II Eagle Butte coal at three different stoichiometric ratios	7-100
7.4-2	CCSEM ash particle size distributions generated by combustion of Phase II Kentucky #9 coal at three different stoichiometric ratios	7-101
7.5-1	Schematic diagram of UA combustor, showing PCSV-P sampling locations	7-104
7.5-2	Illinois #6 cumulative mass distributions measured with the PCSV-P at UA	7-105
7.5-3	Fe-Al-Si CCSEM ternary diagram for UA and PSIT Illinois #6	7-107
7.5-4	K-Al-Si CCSEM ternary diagram for UA and PSIT Illinois #6	7-108
7.5-5	Ca-Al-Si CCSEM ternary diagram for UA and PSIT Illinois #6	7-109
7.5-6	Beulah lignite cumulative mass distribution (low load) measured with the PCSV-P at UA	7-110
7.5-7	Beulah lignite cumulative mass distributions (high load) measured with the PCSV-P at UA	7-110
7.5-8	Loy Yang 2301 low load cumulative mass distributions measured with the PCSV-P at UA	7-111
7.5-9	Loy Yang 2301 high load cumulative mass distributions measured with the PCSV-P at UA	7-111
7.5-10	Loy Yang 1953 cumulative mass distributions measured with the PCSV-P at UA	7-112
7.5-11	Differential Beulah Lignite ash particle size distributions (number basis) measured in-situ with the PCSV-P at the University of Arizona	7-113
7.5-12	Cumulative ash particle size distributions (mass basis) measured in-situ at with the PCSV-P at UA	7-113

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.6-1	Schematic diagram of the SECV 35 kg/h furnace showing sampling locations	7-115
7.6-2	SEM of parent and treated LY 1953	7-124
7.6-3	CCSEM mineral size distribution for coals tested at SECV	7-128
7.6-4	Beulah lignite ash PSD measured with the PCSV-P, ring 7 combustion chamber centerline	7-130
7.6-5	Beulah lignite ash Na-Al-Si ternary plots by CCSEM showing all particles with $\text{Na} + \text{Al} + \text{Si} \geq 80$ atom %	7-131
7.6-6	Ca-Al-Si ternary for Beulah ash, ring 7 combustion chamber extractive sample	7-133
7.6-7	CCSEM ternary Na-Al-Si diagram for the Beulah coal tested at SECV	7-136
7.6-8	CCSEM ternary Na-Al-Si diagram for Beulah ash sampled in the combustion chamber, ring 7 at SECV	7-136
7.6-9	CCSEM ternary Na-Al-Si diagram for Beulah ash sampled from the horizontal duct at SECV	7-137
7.6-10	CCSEM ternary Na-Al-Si diagram for Beulah ash taken from the ESP hopper	7-137
7.6-11	A comparison of ash particle size distributions for combustion chamber, horizontal duct, and ESP ash measured by CCSEM	7-138
7.6-12	CCSEM ash particle size distributions for the Beulah combustion chamber ash sample, with and without high sulfur content ash particles	7-139
7.6-13	CCSEM ash particle size distributions for the Beulah ESP ash sample with and without high sulfur content ash particles	7-139
7.6-14	CCSEM ternary Ca-Al-Si diagram for the Beulah coal tested at SECV	7-141
7.6-15	CCSEM ternary Ca-Al-Si diagram for Beulah ash sampled in the combustion chamber, ring 7 at SECV	7-141

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.6-16	CCSEM ternary Ca-Al-Si diagram for Beulah ash sampled from the horizontal duct at SECV	7-142
7.6-17	CCSEM ternary Ca-Al-Si diagram for Beulah ash taken from the ESP hopper	7-142
7.6-18	Comparison of PSIT/SECV and PSIT Beulah lignite ash particle size distributions on an area basis	7-144
7.6-19	Beulah lignite mineral size distributions for PSIT and PSIT/SECV samples	7-145
7.6-20	Beulah lignite coal particle size distributions	7-145
7.6-21	Loy Yang 1953 ash PSD measured with the PCSV-P, ring 7 combustion chamber centerline	7-147
7.6-22	Loy Yang 1953 ash PSD measured 50 mm from the wall of the combustion chamber (ring 7) with the PCSV-P	7-148
7.6-23	Na-Al-Si ternary, Loy Yang 1953 extracted from the horizontal duct	7-149
7.6-24	Ca-Al-Si ternary, Loy Yang 1953	7-150
7.6-25	Fe-Al-Si ternary, Loy Yang 1953	7-151
7.6-26	Mg-Al-Si ternary, Loy Yang 1953 ash, horizontal duct	7-152
7.6-27	Zn-Al-Si ternary, Loy Yang 1953 ash, horizontal duct	7-153
7.6-28	Al-Zn-Mg ternary, Loy Yang 1953 ash, ESP	7-154
7.6-29	CCSEM ash particle size distributions for ash collected during combustion of Loy Yang 1953 coal, test 4	7-156
7.6-30	CCSEM ash particle size distributions for ash collected during combustion of Loy Yang 1953 coal, test 1	7-157
7.6-31	Loy Yang 1953 treated ash PSD measured at ring 7 combustion chamber (centerline) with the PCSV-P	7-158
7.6-32	Na-Al-Si ternary, treated Loy Yang 1953 ash	7-159
7.6-33	Ca-Al-Si ternary, treated Loy Yang 1953 ash	7-160

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.6-34	Mg-Al-Si ternary, treated Loy Yang 1953 ash	7-161
7.6-35	Zn-Al-Si ternary, treated Loy Yang 1953 ash	7-162
7.6-36	Al-Mg-Zn ternary, treated Loy Yang 1953 ash	7-162
7.6-37	CCSEM ash particle size distributions for ash collected during combustion of treated Loy Yang 1953 coal, test 3	7-166
7.6-38	Comparison of ash particle size distributions obtained from combustion of three coals and measured with the PCSV-P at SECV	7-167
7.6-39	Comparison of CCSEM ash particle size distributions obtained from combustion of three coals; sample from horizontal duct	7-167
7.6-40	Comparison of CCSEM ash particle size distributions obtained from combustion of three coals; sample from ESP	7-168
7.6-41	Test bank deposits, Beulah Lignite (test 2)	7-169
7.6-42	Combustion chamber (top) and test bank (bottom) deposits, Loy Yang 1953 (test 4)	7-170
7.6-43	Combustion chamber (top) and test bank (bottom) deposits, treated Loy Yang 1953 (test 3)	7-171
7.6-44	Normalized deposit compositions as a function of position for Beulah lignite testing	7-176
7.6-45	Deposit and particle samples for ash generated during combustion of Loy Yang 1953 and treated Loy Yang 1953 at SECV	7-177
7.7-1	Comparison of collection efficiencies for Phase I coals at 1500 K combustion gas temperature	7-179
7.7-2	Illinois #6 ash Ca-Al-Si ternary diagram	7-181
7.7-3	Beulah Ca-Al-Si ternary mineral diagram	7-181
7.7-4	Beulah ash Ca-Al-Si ternary diagram: 1500 K, 7% O ₂	7-182
7.7-5	K-Al-Si ternary diagram for nepheline sample	7-183
7.7-6	SEM micrograph showing untreated sample of well-crystallized kaolinite	7-184
7.7-7	SEM micrograph showing kaolinite sample after processing at 1725 K in 3% O ₂ for 2.9s	7-184

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.7-8	Ca-Al-Si ternary diagram for unprocessed montmorillonite sample	7-185
7.7-9	SEM micrograph of raw montmorillonite	7-186
7.7-10	SEM micrograph of montmorillonite after exposure to 3% O ₂ , 1500°C, 1s	7-186
7.7-11	SEM micrograph of montmorillonite after exposure to 3% O ₂ , 1500°C, 2.9s	7-187
7.7-12	SEM micrograph of deposits derived from K-WC at a gas temperature of 1725 K, 3% O ₂	7-189
7.7-13	SEM micrograph of K-WC/montmorillonite 25/75 deposit, 1625 K surface temperature	7-189
7.7-14	SEM micrograph of K-WC/montmorillonite 50/50 deposit, 1625 K surface temperature	7-190
7.7-15	SEM micrograph of nepheline deposits collected at a temperature of 1350°C	7-190
7.7-16	Sticking efficiencies of various Phase II mineral samples compared to San Miguel lignite	7-191
7.7-17	Collection efficiency measurements for Loy Yang 1953	7-192
7.7-18	Collection efficiency, Illinois #6 SOAP	7-193
7.7-19	Comparison of collection efficiencies for program coals at 1500 K	7-194
7.7-20	K-Al-Si Ternary diagram for Gravimelt 7A ash deposit obtained at 1425°C, 21% O ₂	7-196
7.8-1	CCSEM mineral size distributions for Illinois #6 Phase II parent and SOAP coals	7-199
7.8-2	Concentrations of Co and Zn in laboratory combustion ash as a function of ash particle size	7-202
7.8-3	Concentrations of As and Se in laboratory combustion ash as a function of ash particle size	7-202
7.8-4	Concentrations of Sb and Cr in laboratory combustion ash as a function of ash particle size	7-203

LIST OF ILLUSTRATIONS (Continued)

<u>Figure No.</u>		<u>Page No.</u>
7.8-5	Chromium K-edge XANES spectra of two chromic and two chromate oxide reference standards, as determined by the University of Kentucky	7-206
7.8-6	Chromium K-edge XANES spectra of Illinois #6 Phase II parent coal, SOAP beneficiated coal, and a combustion-derived ash sample, as determined by the University of Kentucky	7-206
7.9-1	Flow chart for stochastic fly ash formation code	7-212
7.9-2	Coal PSD for selected coals	7-220
7.9-3	Mineral and ash compositions (Kentucky #11)	7-222
7.9-4	Ash composition: model versus experiments (Kentucky #11)	7-223
7.9-5	Ash PSDs: model versus experiments (Kentucky #11)	7-223
7.9-6	Coal PSDs: actual and fine (Kentucky #11)	7-224
7.9-7	Ash PSD: mode (fine #2) versus experiments (Kentucky #11)	7-224
7.9-8	Ash PSD: model (fine #1) versus experiments (Kentucky #11)	7-225
7.9-9	Mineral and ash compositions (San Miguel Lignite)	7-226
7.9-10	Ash composition: model versus experiments (San Miguel Lignite)	7-227
7.9-11	Ash composition: model versus experiments (San Miguel Lignite)	7-227
7.9-12	Ash PSDs: model versus experiments (San Miguel Lignite)	7-228
7.9-13	Ash composition: model versus experiments (Upper Freeport)	7-228
7.9-14	Ash PSDs: model versus experiments (Upper Freeport)	7-229
7.9-15	Ash composition: model versus experiments (Illinois #6)	7-229
7.9-16	Ash PSDs: model versus experiments (Illinois #6)	7-230
7.9-17	Base/acid ratio variability for Illinois #6 ash particles	7-231
7.9-18	Two-dimensional schematic of interaction region swept out by mineral particles of diameter D_i and D_j during burnout	7-233
7.9-19	Two-dimensional illustration of conical volume swept out by two mineral particles due to spherical shape	7-235
7.9-20	Schematic representation of ash particle formation and release from a cenospheric char particle	7-238

LIST OF TABLES

<u>Table No.</u>		<u>Page No.</u>
3-1	Ash formation issues	3-4
3-2	Coals studied by Phase II principal investigators	3-5
3-3	Illinois #6 SOAP and parent coal analysis	3-7
3-4	Malvern PSD - Illinois #6 Parent	3-8
3-5	Malvern PSD - Illinois #6 SOAP	3-9
3-6	Gravimelt coal sample preparation conditions	3-10
3-7	Gravimelt sample 7A and 9C coal analysis (dry basis)	3-11
3-8	Comparison of Gravimelt sample 7A and 9C coal ash analyses	3-12
3-9	Chemical fractionation of Gravimelt coals	3-12
3-10	Loy Yang 1953 and 2301 coal analyses	3-14
3-11	Eagle Butte and Kentucky #9 parent coal analysis (dry basis)	3-16
3-12	Eagle Butte/Kentucky #9 coal blend analysis: measured versus calculated	3-17
3-13	Malvern measurement of blend coal PSD	3-18
3-14	Fuel analysis for eight Phase I coals	3-19
3-15	Ash chemistry for eight Phase I coals	3-20
3-16	Summary of coal and ash analyses for Phase II coals	3-21
3-17	Summary of CCSEM data for Phase I coals	3-22
3-18	Summary of CCSEM data for Phase II coals	3-23
4-1	Mössbauer data - raw coals	4-36
4-2	Mineralogical data - raw coals	4-37
4-3	Average discrete mineral species composition - Phase I coals	4-38
4-4	Mössbauer data for coals used in new combustion runs	4-42
4-5	Loy Yang 1953 in epoxy psi	4-43
4-6	Beulah SECV/PSIT coal	4-44
4-7	PSIT Illinois #6 parent coal in epoxy (for SOAP #485)	4-47
4-8	PSIT Illinois #6 SOAP coal in carnauba wax	4-48
4-9	Sulfur forms in Gravimelt coals from XANES analysis	4-49

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
4-10	PSIT Powder Nepheline on filter	4-50
4-11	PSIT Powder Montmorillonite on filter	4-51
4-12	PSIT/Arizona Beulah ash on filter 22Im1A, run #2	4-52
4-13	PSIT/Arizona Beulah Lignite ash on filter, Impactor #3, 22IM3	4-54
4-14	PSIT/Arizona Beulah Lignite ash on filter, Impactor #5, 22IM5	4-56
4-15	PSIT/Arizona Beulah Lignite ash on filter, Impactor #7, 22IM7	4-58
4-16	PSIT Beulah ash 7% oxygen on filter paper	4-60
4-17	PSIT Beulah 21% oxygen ash on filter paper	462
4-18	Arizona Eagle Butte ash on filter, Impactor #1, 23IM1	4-64
4-19	Arizona Eagle Butte ash on filter, Impactor #5, 23IM5	4-63
4-20	PSIT/MIT-2 Eagle Butte ash 1750 K, 7%, total filter	4-85
4-21	PSIT pure ash on filter, Kentucky #9, #1G-A, 0.2 g/min, 7% O ₂ , 1500 K	4-70
4-22	PSIT pure ash on filter, Kentucky #9 PSIT #1i, 0.2 g/min, 21% O ₂ , 1500 K	4-71
4-23	PSIT/MIT-4 Kentucky #9 ash, 1750 K, 7% O ₂ , total filter	4-73
4-24	Arizona, Kentucky #9 ash on filter, 24IM1A, impactor #1	4-41
4-25	PSIT K-7 8/4/88 Kentucky #11, 7% O ₂ , 1500 K	4-63
4-26	Arizona, Kentucky #11, ash on filter, 27IM1E, impactor #1	4-78
4-27	Arizona Upper Freeport ash, 32IM1, impactor #1	4-80
4-28	Arizona Upper Freeport ash, 32IM3, impactor #3	4-82
4-29	PSIT/MIT-3 Upper Freeport ash, 1750 K, 7% O ₂ , total filter	4-41
4-30	PSIT pure ash on filter Illinois #6, #if, 7% O ₂ , 0.2 g/min, 1500 K	4-52
4-31	PSIT/MIT-1 Illinois #6 1750 K, 7% O ₂ , total filter	4-74
4-32	Arizona ash on filter, Illinois #6, 21IM1a, impactor #1	4-96
4-33	PSIT #88 San Miguel Lignite DTF ash, 7% O ₂ , 1500 K, 3.0s RST varied	4-91
4-34	PSIT #89 San Miguel Lignite DTF ash 21% O ₂ , 1500 K, 3.0s RST	4-92
4-35	Arizona Illinois #6 ash on filter 1.4 kg/h, 1304°C, impactor #1 + cup	4-93
4-36	Arizona Illinois #6 impactors 2+3+4, 1 kg/h, 1304°C, 11 port	4-95

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
4-37	Arizona Illinois #6 ash on filter 1.4 kg/h, 1304°C, impactors 5+6+7+8+AF	4-97
4-38	Arizona Illinois #6 ash 1304°C, 1.4 kg/h, port 5, impactors #1 + cup	4-96
4-39	Arizona 47D Illinois #6 ash 1304°C, 1.4 kg/h, impactors 2+3+4	4-101
4-40	Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11, impactor #1 + cup	4-103
4-41	Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11, impactors 2+3+4	4-102
4-42	Arizona Illinois #6 ash on filter, 2.4 kg/h, 1368°C, port 11, impactors 5+6+7	4-107
4-43	Arizona Illinois #6 run 47h, 2.4 kg/h, 1368°C, port 5, impactors 1 + cup	4-109
4-44	Arizona Illinois #6 run 47h, 2.4 kg/h, 1368°C, port 5, impactors 2+3+4	4-111
4-45	PSIT/Arizona ash Illinois #6 soap, 1.8 kg/h, port 11, impactor #1 + cup	4-113
4-46	PSIT/Arizona Illinois #6 soap ash, 1.8 kg/h, port 11, impactors 2+3+4	4-115
4-47	PSIT/Arizona Illinois #6 soap, 1.8 kg/h, 1310°C, port 11, impactors 5+6+7+8+AF	4-117
4-48	PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11, impactors #1 + cup	4-119
4-49	PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11, impactors 2+3+4	4-121
4-50	PSIT/Arizona Beulah ash on filter, 1.6 kg/h, 1160°C, port 11, impactors 5+6+7	4-123
4-51	PSIT/Arizona Beulah ash on filter, Sample D, 1.6 kg/h, 1160°C, port 5 IM	4-125
4-52	PSIT/Arizona Beulah ash 1.6 kg/h, port 5, impactors 2+3+4	4-127
4-53	PSIT/Arizona Beulah ash, 2.9 kg/h, 1245°C, port 11, impactors #1 + cup	4-129

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
4-54	PSIT/Arizona ash Beulah, 2.9 kg/h, 1245°C, port 11, impactors 2+3+4	4-131
4-55	PSIT/Arizona Beulah ash on filter, 2.9 kg/h, 1245°C, port 11, impactors 5+6	4-133
4-56	PSIT/SECV Beulah ash probe (combustion chamber) on filter	4-132
4-57	PSIT/SECV Beulah ash probe (horiz. duct.) on filter	4-134
4-58	SECV/PSIT Beulah Lignite precipitator ash collected from electrostatic PR	4-139
4-59	Arizona ash Loy Yang 2301, 2.4 kg/h, 1275°C, port 11, impactors #1 + cup	4-141
4-60	Arizona Loy Yang 2301 ash on filter, 2.4 kg/h, 1275°C, port 11, impactors 2+3+4	4-143
4-61	Arizona Loy Yang 2301, 2.4 kg/h, 1275°C, port 11, impactors 5+6+7+8+AF	4-145
4-62	Arizona ash Loy Yang 2301, 3.8 kg/h, 1420°C, port 11, impactors 1 + cup	4-147
4-63	Arizona Loy Yang 2301 run 49h, 3.8 kg/h, 1420°C, port 11, impactors 2+3+4	4-148
4-64	Arizona Loy Yang 2301 ash, 3.8 kg/h, 1420°C, port 11, impactors 5+6+7+8	4-150
4-65	Arizona Loy Yang 1953, 2.4 kg/h, 1160°C, port 11, impactors #1 + cup	4-152
4-66	Arizona Loy Yang 1953, 2.4 kg/h, 1160°C, port 11, impactors 2+3+4	4-154
4-67	PSIT/Arizona Loy Yang 1953 ash, 2.4 kg/h, 1160°C, port 11, impactors 5+6+7+8+A	4-156
4-68	PSIT/SECV Loy Yang test 1 ash probe (ring 7) on filter untreated	4-158
4-69	PSIT/SECV Loy Yang test 4 ash probe (horizontal duct) untreated on filter	4-160
4-70	SECV/PSIT Loy Yang test #4 precipitator ash collected from electrostatic	4-162

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
4-71	SECV/PSIT Loy Yang test #1 precipitator ash from electrostatic precipitator plate	4-164
4-72	PSIT/SECV Loy Yang treated ash probe (horizontal duct) test 3 on filter	4-166
4-73	SECV/PSIT Loy Yang treated precipitator ash collected from electrostatic	4-168
4-74	PSIT Beulah ash w/o ion exchange, 1s RST (Coal #392)	4-170
4-75	PSIT Beulah ash, w/o ion exchange, 3s RST (Coal #392)	4-169
4-76	PSIT Beulah ash, WITH ion exchange, 1s RST (Coal #392)	4-173
4-77	PSIT Beulah ash WITH ion exchange, 3s RST (Coal #392)	4-176
4-78	Mössbauer results for UA "CUP + IM1" samples (Kentucky #11)	4-178
4-79	Mössbauer data for ash samples from various coals	4-179
5.2-1	Filter characteristics	5-11
5.3-1	Thermal conductivity as a function of temperature and oxygen concentration	5-33
5.3-2	Coefficients for the calculation of the effective thermal conductivity of the boundary layer	5-35
5.3-3	Model results as a function of diameter for 10 and 80% oxygen	5-39
5.3-4	Summary of model results	5-40
5.3-5	Ash composition of the 90 to 106 μm coal samples as determined by inductively coupled plasma emission spectroscopy	5-44
5.3-6	ASTM ash analysis of the raw Phase I coals presented on a sulfur-free basis	5-45
5.3-7	Synthetic chars explored	5-46
5.3-8	Iron, silicon, and calcium content of the 90 to 106 μm sucrose/ carbon black synthetic chars and coals as determined by ICPES	5-51
5.3-9	Fraction of the iron found in the submicron ash	5-52

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
5.3-10	Beulah Lignite mineral size distributions as determined by computer-controlled scanning electron microscopy	5-53
5.3-11	Kentucky #9 Bituminous coal (Phase I, utility grind sample) mineral size distributions as determined by computer-controlled scanning electron microscopy	5-54
5.3-12	Fraction of the silicon found in the submicron ash	5-56
5.3-13	Fraction of the calcium found in the submicron ash	5-57
5.4-1	Ash mass distributions of tested coals by three different modes	5-108
5.4.2	Chemical analysis results on subicron ash	5-109
5.4-3	Synthetic char samples prepared for the study	5-127
5.4-4	Comparison of diameters of ash generated from combustion of different density fractions of Kentucky #9 coal	5-138
5.4-5	Input conditions for simulation runs with the model	5-153
6.1-1	Cut-Off Diameters for Mark II Impactor	6-11
6.1-2	Atomic absorption analysis solution compositions	6-13
6.1-3	Compounds used to prepare 1000 ppm AA standard	6-14
6.3-1	Summary of base case experiments	6-15
6.3-2	Summary of modified temperature profile experiments	6-16
6.3-3	Summary of doped coal burns	6-17
6.3-4	Summary of burns which obtained AA and CCSEM samples, and PCSV particle size distributions	6-18
6.3-5	Summary of burns with cleaned coals and additional baseline coal burns	6-19
6.4-1	Loy Yang 2301 fuel analysis	6-21
6.4-2	Calculated ash analysis for doped and undoped Loy Yang 2301	6-22
6.4-3	Kaolinite analysis	6-23
6.4-4	Calculated ash analysis for doped (with sodium acetate trihydrate) and undoped Kentucky No. 11	6-23
6.5-1	Summary of experiments and acquired samples	6-86

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
6.5-2	Summary of experiments with cleaned coals	6-121
6.5-3	List of samples analyzed by CCSEM	6-134
6.5-4	Most frequent composition in Beulah Lignite fly ash	6-144
6.6-1	Coal compositions for equilibrium calculations on the base suite of coals	6-150
6.6-2	Coal compositions for equilibrium calculation on the cleaned and doped coals	6-160
6.6-3	Coal compositions for surrogate coal systems	6-166
6.6-4	K, Na, and Cl for base suite of coals	6-197
6.6-5	Potassium f_{gA} for Kentucky No. 11	6-201
6.6-6	Summary of illite bench scale experiments	6-205
6.6-7	Average illite composition	6-206
6.7-1	Fraction of condensed sodium	6-217
6.8-1	Comparison of iron analysis for ash from various coals	6-247
6.8-2	Major XRD angles for magnetite and hematite	6-251
6.9-1	Model input parameters	6-262
6.9-2	Silicate melting temperatures	6-263
6.9-3	Experimental parameters	6-270
6.9-4	Simulation results	6-272
7.3-1	Illinois #6 SOAP and parent coal analysis	7-25
7.3-2	Illinois #6 coal: sulfur-containing mineral compositions (mole %)	7-26
7.3-3	Illinois #6 ash chemical composition (SO ₃ -free) (wt% oxides)	7-27
7.3-4	Illinois #6 SOAP ash chemical composition (wt% oxides; SO ₃ -free basis)	7-27
7.3-5	Ash analysis of Illinois #6 SOAP by CCSEM at UNDEERC	7-29
7.3-6	Chemical composition of Illinois #6 SOAP ash by CCSEM	7-30
7.3-7	Coal, mineral, and ash analysis for Loy Yang coals	7-34
7.3-8	Loy Yang 1953 CCSEM mineral analysis	7-35
7.3-9	LY 1953 CCSEM mineral size distributions	7-36

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
7.3-10	Loy Yang 1953 ash chemical composition (wt% oxides; SO ₃ -free basis)	7-37
7.3-11	Loy Yang 1953 ash particle size distributions	7-39
7.3-12	Eagle Butte and Kentucky #9 parent coal analysis (dry basis)	7-41
7.3-13	Eagle Butte/Kentucky #9 coal blend analysis	7-43
7.3-14	CCSEM analysis of Eagle Butte Phase II ash (by UNDEERC)	7-47
7.3-15	Eagle Butte ash chemical composition (wt% oxides)	7-48
7.3-16	CCSEM analysis of Kentucky #9 Phase II ash (by UNDEERC)	7-51
7.3-17	Kentucky #9 ash chemical composition (SO ₃ -free) (wt% oxides)	7-52
7.3-18	CCSEM analysis of blend combustion - generated ash	7-54
7.3-19	Blend ash chemical composition (SO ₃ -free) (wt% oxides)	7-54
7.3-20	Ash compositions of Eagle Butte, Kentucky No. 9, and blend coals by oxide weight percentages	7-56
7.3-21	Gravimelt sample 7A and 9C coal analysis (dry basis)	7-62
7.3-22	Analysis of Gravimelt 7A coal	7-63
7.3-23	CCSEM mineral analysis of Gravimelt 7A	7-63
7.3-24	Average discrete mineral species composition - Gravimelt 7A	7-64
7.3-25	Results of UNDEERC chemical fractionation of Gravimelt 7A coal	7-65
7.3-26	Chemical composition of combustion-generated ash Gravimelt 7A 1700 K, 21% O ₂	7-66
7.3-27	Distribution of iron in Gravimelt 7A minerals	7-73
7.3-28	Gravimelt sample 9C coal analysis (dry basis)	7-83
7.3-29	Chemical fractionation of Gravimelt 9C coal	7-84
7.3-30	CCSEM mineral analysis of Gravimelt 9C	7-84
7.3-31	CCSEM mineral size distributions Parent Pittsburgh #8	7-86
7.3-32	CCSEM mineral size distributions Gravimelt 9C	7-86
7.3-33	Gravimelt 9C average discrete mineral composition	7-86
7.3-34	Chemical composition of combustion-generated Gravimelt 9C ash	7-88
7.3-35	Comparison of surface and cross-sectional CCSEM-87	7-89

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
7.3-36	Fume formation - Kentucky #9	7-95
7.3-37	Fume formation - Kentucky #11 bituminous	7-95
7.3-38	Fume formation - Upper Freeport bituminous	7-95
7.3-39	Fume formation - Eagle Butte sub-bituminous	7-95
7.3-40	Fume formation - Beulah lignite	7-96
7.3-41	Fume formation - San Miguel (Texas) lignite	7-96
7.3-42	Fume formation - Loy Yang coals	7-96
7.3-43	Fume formation - Illinois #6 SOAP	7-97
7.3-44	Fume formation - Gravimelt 7A	7-97
7.3-45	Fume formation - Gravimelt 9C	7-97
7.3-46	Fume formation - Blend of EB/KY 9	7-97
7.4-1	CCSEM ash composition as a function of O ₂ concentration Eagle Butte (wt% of ash)	7-100
7.4-2	Comparison of ash oxide compositions as a function of combustion oxygen level Eagle Butte (wt% as oxides)	7-101
7.4-3	CCSEM ash composition as a function of O ₂ concentration Kentucky #9 (wt% of ash)	7-102
7.4-4	Comparison of ash oxide compositions as a function of combustion oxygen level Kentucky #9 (wt% as oxides)	7-102
7.6-1	Operating parameter ranges for the SECV 35 kg/hr furnace	7-116
7.6-2	Analysis of LY 1953 coal	7-117
7.6-3	Analysis of treated Loy Yang 1953	7-118
7.6-4	Analysis of Beulah coal	7-118
7.6-5	Malvern coal PSD - Beulah	7-119
7.6-6	Malvern coal PSD - Loy Yang 1953	7-120
7.6-7	Malvern coal PSD - treated LY 1953	7-121
7.6-8	CCSEM mineral distributions of coals tested at SECV	7-122

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
7.6-9	CCSEM chemical composition of Loy Yang "unknown" mineral categories: elemental mole%	7-123
7.6-10	Included/excluded mineral analysis of Beulah Lignite coal tested at SECV	7-126
7.6-11	Included/excluded mineral analysis of untreated LY test 4 coal tested at SECV	7-126
7.6-12	Included/excluded mineral analysis of treated Loy Yang 1953 tested at SECV	7-127
7.6-13	Ash chemical composition analysis, SECV tests	7-128
7.6-14	Furnace parameters for SECV coal tests	7-129
7.6-15	Sampling location conditions - Beulah lignite	7-129
7.6-16	Chemical analysis of selected species in bulk ash samples - Beulah lignite	7-133
7.6-17	Crystalline phases observed in Beulah lignite testing - XRD analysis	7-134
7.6-18	Comparison of CCSEM and AA ash compositions Na and Mg free basis for Beulah lignite ash samples	7-135
7.6-19	Sulfur content of ash particle samples (CCSEM)	7-140
7.6-20	Major Na and Ca ash compositions identified by CCSEM (vol%)	7-143
7.6-21	Mossbauer analysis of SECV Beulah ash samples	7-144
7.6-22	Sampling location conditions - Loy Yang 1953, Test 1	7-146
7.6-23	Sampling location conditions - Loy Yang 1953, Test 4	7-147
7.6-24	Chemical analysis of Loy Yang 1953 Test 4 ash and deposit samples	7-155
7.6-25	Crystalline phases observed in Loy Yang 1953 Test 4 - XRD analysis of ash and deposits	7-155
7.6-26	CCSEM chemical composition analysis of Loy Yang 1953 Test 4 samples	7-156
7.6-27	Sampling location conditions - treated Loy Yang 1953, Test 3	7-158
7.6-28	Chemical analysis of treated Loy Yang 1953 Test 3 ash and deposit samples	7-163

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
7.6-29	Crystalline phases observed in Loy Yang 1953 (treated) testing - XRD analysis	7-163
7.6-30	CCSEM analysis of treated LY 1953 samples (Test 3)	7-165
7.6-31	CCSEM chemical composition analysis of treated LY 1953 samples (Test 3)	7-166
7.6-32	Cascade impactor data for ash samples obtained in SECV tests	7-168
7.6-33	Crystalline phases observed in deposition test bank 1 samples - XRD analysis	7-172
7.6-34	Crystalline phases observed in deposition test bank 3 samples - XRD analysis	7-173
7.6-35	Crystalline phases observed in ceramic deposition probe samples - XRD analysis	7-173
7.6-36	Crystalline phases observed in cooled deposition probe samples - XRD analysis	7-174
7.6-37	Chemical analysis of Beulah (Test 2) ash and deposit samples (wt%)	7-175
7.7-1	Mineral sample chemical composition	7-182
7.7-2	SEM/EDX analysis of Montmorillonite high-temperature deposit sample	7-188
7.7-3	Summary of stickiness testing results for Phase II coals, lower tube	7-192
7.7-4	Illinois #6 SOAP deposit compositions by SEMPC	7-193
7.7-5	Gravimelt 7A ash and deposit chemical composition	7-195
7.7-6	Stickiness testing of Gravimelt 9C (as-received coal, 21% O ₂)	7-197
7.7-7	Gravimelt 9C deposit composition 1500°C, 21% O ₂	7-197
7.8-1	Concentrations of trace elements in U.S. coals	7-198
7.8-2	Forms of trace elements in coal	7-198
7.8-3	Trace element analysis, Illinois #6 Parent and ash	7-200
7.8-4	Trace element analysis, Illinois 6 SOAP and ash	7-200
7.8-5	Trace element analysis, Beulah coal and ash	7-201
7.8-6	Chromium concentrations in coals of different rank	7-204
7.9-1	Simulated coal and mineral particle distributions for Illinois #6	7-211

LIST OF TABLES (Continued)

<u>Table No.</u>		<u>Page No.</u>
7.9-2	Mineral inventory of some selected fly ash particles	7-214
7.9-3	Elemental composition and area percent of full computer-generated fly ash sample for San Miguel Lignite based on limited coalescence of 16, 30, and 60 μm minerals	7-216
7.9-4	Size distributions for full computer-generated fly ash sample for San Miguel Lignite based on limited coalescence of 16, 30 and 60 μm inclusions	7-217
7.9-5	Elemental composition and area percent of randomly selected subset of computer-generated fly ash particles for San Miguel Lignite based on limited coalescence of 16, 30, and 60 μm inclusions	7-218
7.9-6	Size distributions for randomly selected subset of computer-generated fly ash particles for San Miguel Lignite based on limited coalescence of 16, 30 and 60 μm inclusions	7-219
7.9-7	Mineral size distribution data - raw coals	7-221
7.9-8	Size distribution for each fly ash type (number % in each fly ash type) for Illinois #6 coal	7-240
7.9-9	Coal particle number distribution and number of ash particles produced for Illinois #6 coal	7-241

LIST OF ACRONYMS

AA	Atomic Absorption Spectroscopy
ASTM	American Society for Testing and Materials (standards)
CC	Combustion Chamber (in the SECV test furnace)
CCSEM	Computer-controlled Scanning Electron Microscopy
CMA	Coal Minerals Analysis
DOE/PETC	DOE - Pittsburgh Energy Technology Center
DTF	Drop Tube Furnace
EDX	Energy Dispersive X-ray Analysis
EM	Engineering Model (for ash formation)
ESP	Electrostatic Precipitator
EXAFS	Extended X-ray Absorption Fine Structure
FEGT	Furnace Exit Gas Temperature
FWDC	Foster Wheeler Development Corp.
HD	Horizontal Duct (in the SECV test furnace)
ICPES	Inductively-coupled Plasma Emission Spectroscopy
IM-i	Cascade Impactor Sample from stage i
LIPF	Laser-Induced Photodissociation and Fluorescence
LTA	Low Temperature Ash
LY	Loy Yang (coal)
MIT	Massachusetts Institute of Technology
MM	Mineral Matter
NAA	Neutron Activation Analysis
PCSV-P	Particle Counter-Sizer-Velocimeter (-probe)
PEG	polyethylene glycol
psd	particle size distribution
PSIT	PSI Technology Co.
RSF	Radial Structure Function
SECV	State Electricity Commission of Victoria, Australia
SEM	Scanning Electron Microscopy
SOAP	Spherical Oil Agglomeration Product
SR	Stoichiometric Ratio
STEM	Scanning Transmission Electron Microscopy
TF	Total Filter (sample type)
UA	University of Arizona
UK, UKY	University of Kentucky
UNDEERC	University of North Dakota Energy and Environmental Research Center
USGS	U.S. Geologic Survey
XAFS	X-ray Absorption Fine Structure (spectroscopy)
XANES	X-ray Absorption Near Edge Structure
XRD	X-Ray Diffraction
ZAF	atomic number / absorption / fluorescence (correction)

1. EXECUTIVE SUMMARY

The inorganic constituents or ash contained in pulverized coal significantly increase the environmental and economic costs of coal utilization. For example, ash particles produced during combustion may deposit on heat transfer surfaces, decreasing heat transfer rates and increasing maintenance costs. The minimization of particulate emissions often requires the installation of cleanup devices such as electrostatic precipitators, also adding to the expense of coal utilization.

Despite these costly problems, a comprehensive assessment of the ash formation and deposit initiation processes had never been attempted. At the start of this program, it was hypothesized that ash deposition and ash particle emissions both depended upon the size and chemical composition of individual ash particles. Questions such as: What determines the size of individual ash particles? What determines their composition? Whether or not particles deposit? How combustion conditions, including reactor size, affect these processes? remained to be answered. In this 6-year multidisciplinary study, these issues were addressed in detail. The ambitious overall goal was the development of a comprehensive model to predict the size and chemical composition distributions of ash produced during pulverized coal combustion.

Before this could be attempted, each of the steps in the ash formation process needed to be examined individually. In this project, this was accomplished by distributing responsibility among the various team members. This distribution of efforts is illustrated on an ash formation pathway schematic diagram in Figure 1-1.

As a result of the efforts of this program, the importance of the individual steps illustrated in Figure 1-1 is now known in considerable detail. For example, it has been shown that excluded minerals can significantly affect the size and composition of the ash particles. Char fragmentation, on the other hand, was found to have little influence on these distributions for all but the lowest ash ($< 5\%$) coals. Alkali vaporization was found to be affected by the presence of aluminosilicate minerals, with the formation of alkali aluminosilicates retarding alkali vaporization. Calcium-rich aluminosilicates were found to lead to significant particle deposition under a wide range of conditions. Pyrite-derived ash particles were also found to deposit over a wide range of conditions, provided that a molten phase was present.

These findings, as well as the development of a comprehensive predictive model for ash size and composition, are summarized in the Phase 1 Final Report issued March 1990, and in this document, the Phase 2 Final Report. A comprehensive summary of all of the findings from both phases of this program is provided in the remainder of this Executive Summary.

FIGURE 1-1. - Schematic diagram of ash formation process showing areas addressed by this program.

The technical objectives of this project were:

- a. To: 1) define the partitioning of inorganic constituents associated with raw coal particles among products (including vapors, aerosols, and residual char/ash particles) formed under conditions representative of pulverized coal flames as a function of the specific (intrinsic and extrinsic) characteristics of the raw coal and the environment in which the transformations occur; and 2) characterize the resultant spectrum of products in detail.
- b. To elucidate and quantify the fundamental processes (involving basic principles of physics, chemistry, and thermodynamics) by which the transformations of the inorganic constituents occur.
- c. To develop, based on the information required in a. and b. above, a tractable "process" model capable of predicting the significant features of the transformation process, most importantly, the nature and distribution of ash products.

Phase 1 of this program, which extended from October 1986 - December 1989, focused on inorganic transformations for "raw" coals of differing rank. Phase 2 of this program, which extended from January 1990 - September 1992, focused on inorganic transformations for beneficiated and blended coals.

This report provides a complete description of data collected and conclusions reached during Phase 2 of this program. Phase 1 results were compiled previously in a Final Report submitted to DOE/PETC in March of 1990, although many of the important conclusions are also discussed herein. The breakdown of this report is as follows: Section 1, the Executive Summary, identifies highlights from the entire 6-year program. Section 2 provides a description of the approach and objectives of each individual task during Phase 2. Section 3 presents a compilation of Phase 2 coal analytical data, with summaries of Phase 1 coal data included for comparison. In Section 4, coal mineral and ash analytical results obtained by the University of Kentucky using CCSEM, Mössbauer, and XAFS spectroscopy on Phase 2 samples are reported. Phase 1 coal mineralogical data are also summarized in this section. In Section 5, the results of a study at the Massachusetts Institute of Technology (MIT) to measure the importance of char fragmentation and inorganic species vaporization in determining the ash particle size and composition distributions are reported. Section 6 contains a description of combustion experiments conducted in a self-sustained combustion facility at the University of Arizona, with emphasis on the fate of alkali species and iron during ash formation. Finally, Section 7 presents the results of PSI Technology Company (PSIT) experimental and modeling work. Baseline testing results for the Phase 2 coals are presented, and tests conducted to determine ash and pure mineral particle stickiness are described. Two specialized testing programs, designed to assess 1) the impact of beneficiation on trace element evolution, and 2) the effect of combustion scale on ash formation, through joint testing conducted with the State Electricity Commission of Victoria (SECV), are also discussed. Finally, the Phase 2 development of an overall "Engineering Model" to predict the size and composition distributions of ash particles formed during pulverized coal combustion is described in Section 7.

Significant conclusions reached during this program include:

- For all coals and conditions, a broad distribution of ash particle chemical compositions is obtained. Hence, "mean" ash compositions may be meaningless.
- The most important factors determining ash size and chemical composition distributions are mineral size, mineral type, the coalescence of included minerals, and the fragmentation of excluded minerals.
- Char fragmentation has little effect on the ash particle size distribution for all but very low ash coals (< 5% ash).
- Calcium-rich aluminosilicate particles form from combustion of coals with large concentrations of organically associated calcium.

- Iron aluminosilicate formation occurs to only a very limited extent during pulverized coal combustion.
- The amount of sodium condensing on the smallest ash particles is affected by the amount of aluminosilicates present in a coal. In other words, the amount of sodium available for "fouling" is proportional to the sodium to aluminosilicate ratio in a coal, and *not* dependent on the total amount of sodium.
- The amount of potassium vaporizing depends upon the amount of sodium vaporizing.
- Pyrite reacts to form several molten intermediates before finally oxidizing to magnetite and hematite. It is these intermediate products that contribute to iron slagging in utility boilers.
- Calcium aluminosilicate ash particles are the stickiest compositions when inertial impaction-driver deposition is considered.
- Experiments conducted at bench through pilot scale facilities indicated that combustion scale did not affect any of the conclusions. The same factors dominating ash formation for a particular coal at the bench scale were important at the 1 million Btu/h scale.

These topics, associated modeling, and the processes of coal selection and characterization are discussed further in the following paragraphs. Details are provided in the text of the report as noted.

The notation " $\Phi 1$ " indicates an accomplishment of Phase 1 of this program; details can be found in the Phase 1 Final Report. Similarly, the notation " $\Phi 2$ " indicates an accomplishment of Phase 2 of this program, which is discussed in more detail in subsequent sections of this report.

- (1) **Coal Selection** Seven U.S. coals were selected and acquired for Phase 1 of this program. The selection criteria included coal mineralogy and utility operating experience; that is, coals were chosen to highlight minerals and mineral combinations believed to cause deposition in full scale utility boilers. Coals containing pyrite, illite, other aluminosilicates, calcite, and organically associated calcium and alkali metals were chosen. These coals included four bituminous coals, to study the transformations of pyrite, illite, and calcite: Upper Freeport (Pennsylvania) from the Appalachian Basin, Kentucky #9, Kentucky #11, and Illinois #6 from the Illinois Basin; one sub-bituminous coal, to study the role of organically-associated calcium: Eagle Butte, from the Powder River Basin; and two lignites, to study the roles of sodium and aluminosilicate minerals including kaolinite: Beulah (North Dakota), from the Great Plains Region, and San Miguel (Texas), from the Gulf Coast Lignite

Region. In addition, an Australian brown coal was also acquired from the State Electricity Commission of Victoria to study the behavior of sodium and chlorine in low ash content coals: Loy Yang, (bore) 2301. Australian Lochiel (lignite) coal was also studied to a limited extent. (Φ1)

- (2) ***Coal Preparation and Distribution*** All of the Phase 1 coals were pulverized to a nominal size of 70 weight percent passing through a 200 mesh screen, riffled, and distributed to the Principal Investigator (PI) of each task. Sample preparation procedures were designed to provide an identical coal sample to each PI, through centralized acquisition, preparation, and distribution by R. Bryers of Foster Wheeler Development Co. This was verified by performing ultimate, proximate, and ash chemical analyses on the every coal sample sent to each PI. Analytical results for all barrels of all seven of the U.S. coals tested were demonstrated to be in excellent agreement, confirming the uniformity of coal samples among all researchers in this program. This was a critical aspect of the program, for it enabled the various research teams to examine the effects of combustion scale and combustor type on ash particle size and composition distributions directly from intercomparison of results. Constancy of coal particle size distribution (psd), critical in minimizing any particle-to-particle differences in ash content or composition, was also assured by this methodology. Because of a more limited testing program, the Loy Yang Australian coal was pulverized by SECV for PSIT and MIT, but was pulverized by the University of Arizona (UA) for UA testing. Differences in Loy Yang coal psd between UA and MIT/PSIT were not expected to affect the comparison of results, however. The vast majority of inorganic species contained in Loy Yang are organically associated, so coal particle to coal particle differences in ash content and composition were expected to be minimal for this coal only. (Φ1)
- (3) ***Beneficiated Coal Selection*** In Phase 2 of this program, emphasis shifted to an examination of the ash formation process during the combustion of beneficiated and blended coals. Beneficiation processes are generally expected to remove the largest minerals from coal, as large minerals tend to appear in the densest coal particles. High density minerals such as pyrite are also expected to be removed. Removal of the largest minerals will certainly affect the amount and size distribution of fly ash produced; it can also affect the *composition* distribution. If any minerals are enriched in the largest size range, their removal will certainly affect the overall chemistry of the ash, with the extent depending upon the amount of ash removed (and thus on the cleaning process chosen).

Eight coals were therefore selected to examine the impacts of blending and beneficiation in Phase 2. These included: a new Illinois #6 parent coal, and a physically beneficiated sample of this coal - Illinois #6 spherical oil agglomeration product (SOAP), to study the effects of beneficiation on a particular bituminous coal; a new Eagle Butte parent coal, a new Kentucky #9 parent coal, and a 70/30 wt/wt Eagle Butte/Kentucky #9 blend, to study the role of coal blending on ash formation; two chemically beneficiated coals, cleaned by molten caustic leaching, to study ash

formation in advanced ultra-low ash ($< 1\%$) fuels - Pittsburgh #8 (Gravimelt 9C), and Kentucky #9 (Gravimelt 7A); and finally, a higher ash Loy Yang sample from bore 1953, generally to simulate chemical beneficiation of a low-ash coal, and specifically to examine further the role of aluminosilicates on alkali evolution through direct comparison with Loy Yang 2301 data.

Because of the developmental nature of the beneficiation processes considered, a different strategy for coal distribution was pursued in Phase 2. Chemically beneficiated coals were acquired and prepared by DOE/PETC, and distributed to the various PI's directly. The SOAP fuel was obtained from ABB/Combustion Engineering, who are studying the fuel under a separate program. The blend and blend parent coals were acquired, prepared, and distributed by UNDEERC through a cooperative agreement with DOE/PETC, in much the same manner as the Phase I coals were distributed. Loy Yang 1953 was provided by SECV in pulverized form to all Phase 2 PI's. Additional information on coal acquisition for Phase 2 fuels is provided in Section 3 of this report. (Φ2)

- (4a) ***Coal Mineralogical Characterization - "Raw" Coals*** Having established the uniformity of the coals supplied to each PI, a single sample of each was analyzed by computer controlled scanning electron microscopy (CCSEM) to determine the type, composition, and size of the coal mineral matter. Most coals were also analyzed by Mössbauer spectroscopy techniques to provide more accurate data on the forms of iron in coal. This was of particular value in cases where the iron was partially oxidized, as CCSEM does not routinely identify elements lighter than sodium (e.g., oxygen).

For the Phase 1 coals, CCSEM indicated that the bituminous or "Eastern" coals contained primarily quartz, pyrite, and illite (a potassium aluminosilicate), with varying levels of kaolinite (an aluminosilicate). Illinois #6 was the only one of the four to contain appreciable levels (7%) of the mineral calcite. Low-rank or "Western" coals contained principally quartz, kaolinite, and organically associated sodium and calcium. San Miguel lignite was unique among the seven in containing large quantities of zeolites. Quartz, silicates, and an oxidized iron phase were the only minerals detected in the high sodium, approximately 2% ash content Loy Yang 2301. Most of the iron in all Phase 1 coals except Upper Freeport was pyritic; small amounts were found in clays and carbonates for the bituminous coals, and in oxidized form (possibly oxyhydroxide) for the Eagle Butte sub-bituminous coal. Mössbauer analysis of the Upper Freeport indicated 7% of the iron was present as siderite, 11% as Fe^{2+} clays, and 3% as jarosite. All of the iron in Loy Yang 2301 was in an oxidized form, likely FeOOH . (Φ1)

Low temperature oxygen ashing was also performed on Phase 1 coals to provide samples for x-ray diffraction (XRD) mineral analysis. For most coals, XRD mineralogy was in agreement with CCSEM mineralogy. For the Eagle Butte coal

only, much higher calcite levels were reported by XRD. A detailed discussion of these results was presented in the Phase 1 Final Report. (Φ1)

- (4b) ***Coal Mineralogical Characterization - Beneficiated Coals*** For the Phase 2 coals, CCSEM indicated that coal preparation strongly affected the resultant ash composition and coal mineralogy. Illinois #6 parent coal was similar in ash composition to the Phase 1 parent. Mineralogical analysis also yielded similar results, although the Phase 2 sample had smaller minerals, and approximately 1/2 of the pyrite of the Phase 1 Illinois #6. Beneficiation to prepare the SOAP product, however, produced significant changes. Ash content was reduced from 9.9 to 3.6%, quartz was reduced at a greater rate than other minerals, and correspondingly, the silica content of the ash decreased. The ultra-low ash (<1%) chemically beneficiated Gravimelt coals showed slight retention of quartz and pyrite-derived mineral phases, although most of the mineral matter was removed during caustic leaching. The remaining inorganics were enriched in alkali and titania as compared to generic "parent" Pittsburgh #8 and Kentucky #9 coals, suggesting retention of alkali during the leaching process, and an inability to remove finely dispersed titanium (form uncertain). Interestingly, the mineral size distribution of the Gravimelt 7A (Kentucky #9-derived) sample was larger than expected, being comparable to mineral psd's of several Phase 1 parent coals. The Gravimelt 9C retained only the smallest minerals. The Loy Yang 1953 was, as expected, similar to the Loy Yang 2301, with silicates, quartz, and an oxidized iron phase dominating the mineralogy. Sodium-in-ash concentrations were lower for the Loy Yang 1953 than for the Loy Yang 2301. For the Eagle Butte/Kentucky #9 blend, most measured coal properties were comparable to levels calculated from the parent coal analyses and the blending ratio. The mineral size distribution for the blend was comparable to that of the Eagle Butte in the larger sizes; for minerals < 10 μm, it was intermediate to the two parent coals. Most mineral amounts fell between the bounds imposed by the parent coals, although pyrite levels (as a fraction of the mineral matter in the blend) measured by CCSEM were surprisingly high. Because iron oxide concentrations in the ash were at the expected levels, it is assumed that the CCSEM overestimated the pyrite content of this blend. Further discussion of these coals and detailed summaries of Phase 1 coals are provided in Sections 3, 4, and 7.3 of this report. (Φ2)

Phase 2 samples were also analyzed by Mössbauer to obtain more quantitative information on the forms of iron. Although CCSEM suggested that roughly 15% of the iron was present as pyrite in Illinois #6 SOAP coal, Mössbauer suggested a complete absence of pyrite. Instead, jarosite (a sulfated iron compound) and iron oxyhydroxide were suggested as the dominant phases. Iron in the Loy Yang 1953 coal was primarily in oxyhydroxide form, similar to the Loy Yang 2301 examined in Phase 1. The Beulah coal examined at SECV showed little evidence of weathering; Mössbauer analysis indicated 100% pyrite, while CCSEM suggested small amounts (< 10% of the iron) of iron sulfates. No pyrite was detected in the chemically treated Gravimelt coal samples, although sulfur analysis suggested the presence of elemental sulfur, sulfonate, and sulfate, all of which were absent from the parent

coal. Interestingly, both CCSEM and Mössbauer suggested partial oxidation of the pyrite in the Kentucky #9 and Illinois #6 Phase 2 coals. Results are presented in more detail in Section 4 of this report. (Φ2)

- (5) **Forms of Calcium in Coal** Calcium forms in all of the Phase 1 coals were analyzed by x-ray absorption fine structure spectroscopy (XAFS). For the three low-rank coals examined, near-edge XAFS analysis (XANES) suggested that calcium was predominantly bound as cations to carboxyl groups in the coal macerals. Calcium in the four Phase 1 bituminous coals was approximately equally partitioned between the mineral calcite and carboxyl-bound calcium. (Φ1)
- (6) **Forms of Chlorine in Coal** XANES analysis of the forms of chlorine in Loy Yang and in Illinois #6 coals indicated that chlorine is primarily anionic, dissolved in the inherent moisture in the coal. There was no evidence of crystalline chlorides in any of the untreated coal samples examined. Upon slow in-situ heating to temperatures above 250°C in the XAFS cell, however, a high chlorine sample (0.84%) of Illinois #6 showed evidence of the formation of crystalline sodium chloride. No changes were observed in slow heating of a lower (0.32%; more typical) chlorine sample of Illinois #6. (Φ1,2)
- (7) **Coal Gravity Fractionation** Size and gravity fractions of Beulah lignite and Upper Freeport coals were analyzed by Mössbauer and CCSEM techniques during Phase 1. Results were more complex than had been anticipated previously in the absence of detailed information. Evidence from analysis of both coals clearly indicated that the efficiency of the gravity fractionation process decreased with decreasing mesh size, as less variation among the fractions was observed for the finer mesh sizes (smaller particles). For the Upper Freeport samples, at least two distinct populations of pyrite minerals were present: one rather coarse and associated with large quartz and illite minerals; the other, smaller and well dispersed throughout the organic matrix of the coal. In contrast, pyrite in the Beulah lignite occurred almost entirely as large isolated minerals. A detailed discussion of this study was presented in Section 4.3.2 of the Phase 1 Final Report. (Φ1)
- (8) **Ash Particle Size Distributions** Ash particle size distribution measurements were conducted for each of the program coals. In general, results obtained at PSIT, MIT, and UA all demonstrated a bimodal size distribution, with a distinct peak in the submicron size range. Residual ash or fly ash, consisting of discrete excluded minerals and coalesced included minerals, comprised the supermicron size mode. Evidence for mineral fragmentation (pyrite and calcite) was obtained for several coals. The large size mode was controlled by the amount, size, and type of excluded minerals, the fragmentation of excluded minerals, and the extent of coalescence of included minerals. Char fragmentation was generally not a dominant factor, although its importance depended strongly upon the ash content of a coal (see item number 10 in this section). The residual or fly ash particle size distribution was therefore bounded on the large end by the creation of one ash particle per coal particle (i.e.,

complete mineral coalescence). As a lower bound, mineral fragmentation occasionally led to a final ash psd smaller than the initial mineral size distribution. One ash particle per mineral inclusion is therefore not always an appropriate bound, particularly for coals with large amounts of excluded pyrite. The submicron ash mode was formed principally by the vaporization of inorganic species, followed by nucleation, coagulation, and surface condensation. Detailed discussion of these phenomena are provided in the Phase 1 Final Report and in Sections 5 (vaporization, char fragmentation), 6 (alkali vaporization), and 7 (mineral coalescence) of this report. (Φ1,2)

- (9) ***Mineral Coalescence - Chemical Composition Distributions of Ash Particles*** One of the most important results from this program was the characterization of the fly ash particle composition distributions. For all coals examined, including the < 1% ash content chemically cleaned coals, a broad distribution of ash particle compositions was obtained. This finding clearly indicates that the assumption of a single "mean" size and "mean" composition is a poor representation of combustion-derived ash.

Several key mineral interactions were also identified as being major contributors to the observed ash particle composition distributions. For bituminous coals, coalescence among kaolinite, illite, and other mixed composition aluminosilicates occurred for most included minerals. This was important for determining size and composition, although deposition testing indicated that the behavior of iron, and in particular the formation of iron-aluminosilicates was important for ash deposition. Pyrite-derived iron-aluminosilicate formation was inferred from the data, but a detailed study at UA suggested that the dissolution of iron in aluminosilicate melts was generally incomplete. For low-rank coals, the behavior of calcium and sodium, and their interactions with aluminosilicate minerals, were critical in determining the composition distributions and stickiness of combustion-derived ash. In all coals with high concentrations of organically-associated calcium, a calcium-rich aluminosilicate layer coated the surface of most aluminosilicate ash particles. This suggested incomplete mixing of the calcium in the ash particle during the time scale of combustion. Sodium aluminosilicate formation, corresponding in composition to the mineral nepheline, was also observed for the high sodium Beulah lignite studied.

The beneficiated Illinois #6 SOAP and the blended coal demonstrated the mineral interactions that would have been expected, given the composition of the parent coals. Differences appeared to be related to the amount of a given mineral remaining in the fuel; no significant changes in interacting minerals were identified. For the chemically cleaned Gravimelt coals, however, the removal of most of the major mineral species led to the formation of some titanium aluminosilicates not observed elsewhere. This suggested the presence of fine grained or organically associated titanium that was not removed by cleaning.

The results of the mineral interactions study are highlighted in Section 4, and described in detail in Sections 6 and 7 of this report. (Φ1,2)

- (10) **Effects of Combustion Scale** In both phases of this program, experiments with identical coals were conducted at MIT, PSIT, and UA. Each facility, however, has experimental reactors of different scale. The isothermal drop tube furnace facility at MIT was designed for fundamental studies using a dilute stream of coal particles, at essentially infinite excess oxygen conditions. Narrowly size-segregated coal samples were used, with gas temperature controlled through electrical heating of the reactor walls. Coal particle feed rates of 0.001 to 0.02 kg/h were typical (i.e., 500 Btu/h or 150 W_{th} maximum). At PSI Technology Co., a laminar flow isothermal drop tube furnace was also used, with some important distinctions. First, the reactor was preceded by a methane/air burner that preheats the gases. Second, higher coal particle number densities in the gas were achieved, permitting operation at stoichiometric ratios from 10 to 1 and below. Finally, "utility grind" coals - nominal 70% through 200 mesh screen - could be fired directly. Experiments were conducted at feed rates of 0.03 to 0.3 kg/h, corresponding to approximately 8,000 Btu/h (2.3 kW) maximum. At the University of Arizona, a plug-flow, self-sustained, downfired combustor was used in combustion testing. No auxiliary heating was supplied to the combustor during test burns. Temperature profiles were those occurring naturally as a result of combustion of the coal. Stoichiometric ratios of 1.2 at nominal feed rates of 1.8 to 4 kg/h (approximately 50,000 to 100,000 Btu/h, or 15 to 30 kW) were routinely employed.

With these facilities and the use of identical coal samples, the effects of combustion scale could be directly examined. It was found that ash particle size and chemical composition distributions agreed well if combustion conditions were comparable at the three facilities. That is, if coal particle combustion temperatures were comparable at PSIT and UA, particle size distributions were found to be in good agreement with one another (comparison with MIT results was not made because of the differences in coal psds). Within narrow bounds (i.e., 7% to 21% oxygen, or stoichiometric ratios of approximately 1.5 to 4.5), little change was noted in the size or composition of the ash for the four coals examined under these conditions. Examination of the composition distribution at the three facilities revealed that similar ash phases were formed in all. It was observed, however, that the amount and composition of the submicron ash fume was much more sensitive to differences in combustion conditions, coal particle size distribution, and temperature history. The amount of fume generated at MIT in the dilute experiments was routinely the highest, and increased significantly with increasing oxygen partial pressure. PSIT and UA facilities showed comparable lower levels.

From this analysis, it was concluded that *coal mineralogy* and combustion temperature are the most important parameters determining the composition distribution of combustion-derived fly ash particles. Results are described in both the Phase 1 and Phase 2 Final Reports, and discussed in most sections. (Φ1,2)

- (11) **Char Fragmentation** An extensive study of the role of char fragmentation in determining the ash particle size distribution was conducted by MIT. Mechanistic

experiments using size and density classified coals, chars devolatilized at different heating rates to produce differing pore structures, and synthetically produced chars were used to examine the effects of coal ash content and char macroporosity on fragmentation. High ash content coals such as San Miguel lignite and Kentucky #9, and low macroporosity chars were found to produce approximately 1 ash particle per coal particle. Coals with low mineral content such as Eagle Butte and Loy Yang were more heavily influenced by char fragmentation. Samples of size-classified Kentucky #9 with different pore structures confirmed that low ash content and macropores were required before char fragmentation could significantly influence the ash particle size distribution. It was therefore concluded that macropores were necessary for char fragmentation to occur, and were important in limiting the coalescence of ash particles on the surface of the burning char particles. It was also concluded that the effect of pore structure on char fragmentation was only significant when the coal ash content was below approximately 5%; at higher levels, char fragmentation was not an important mechanism in shaping the final ash psd. This confirms an earlier hypothesis that char fragmentation would become more important for deeply beneficiated coals. The results of this study are presented in detail in Section 5 of this report. (Φ1,2)

- (12) ***Effect of Reducing Conditions*** Limited Phase 2 experimentation was conducted at PSIT to explore the impact of reducing conditions on ash formation. In a series of experiments with Phase 2 Eagle Butte and Kentucky #9 coals, gas temperature was held constant at 1650 K while the stoichiometric ratio was varied from 0.9 to 3.4. Examination of the ash by CCSEM revealed that for each coal, changing stoichiometry had little effect on the particle chemical composition distributions. In all cases, however, the amount of submicron fume increased with increasing oxygen level, a result of the increase in particle combustion temperature with increasing O_2 . These results suggest that conditions more severely reducing than $SR = 0.9$ may be required to affect coalescence and fly ash particle composition. Results are described in Section 7 of this report. (Φ2)
- (13) ***Pilot Scale Testing at SECV*** Under an IEA Annex I Agreement, researchers at PSIT collaborated with researchers at the State Electricity Commission of Victoria (SECV) in pilot scale tests of three low-rank coals. Beulah lignite, Loy Yang 1953, and a chemically treated sample of LY 1953 were studied in the SECV 1,000,000 Btu/h (0.3 MW_{th}) combustor. Loy Yang and treated Loy Yang tests were designed to assess deposition and deposit control, whereas Beulah tests were designed to assess ash formation for comparison with earlier program results. The Beulah lignite coal was provided in crushed form by this program; thus, it was identical in mineral and ash *content* to the coals examined at PSIT, UA, and MIT. Coal and mineral size distributions differed from those tested at the other facilities, however, because of the difference in pulverizers used. Direct size comparisons among facilities were therefore not expected to be conclusive; ash particle composition comparison could, however, be made if no significant differences in mineral distribution resulted from the differences in pulverization. These tests therefore provided an opportunity to

further assess the mechanisms of ash particle formation and deposition, and determine again whether combustion scale (and the associated temperature profile) affected our conclusions.

Ash particle samples were collected isokinetically from the combustion chamber, from the horizontal duct upstream of the deposition test banks (i.e., convective section), and from the electrostatic precipitator hoppers. Examination of Beulah lignite ash samples revealed nepheline-like sodium aluminosilicate compositions similar to those observed in PSIT and UA testing of this coal. Calcium aluminosilicate compositions similar to those observed during Beulah testing at PSIT and UA were also observed. Calcium sulfate-sodium sulfate solid solutions, identified previously in smaller ash particles collected in UA tests, were also seen in the smaller ash particles here.

These results provide confirmation of the conclusion drawn from a prior comparison of PSIT/UA results, and examination of the effects of variable stoichiometry. In all systems examined, from 0.15 kW_{th} to 0.3 MW_{th}, using a common Beulah lignite coal, that ash particle composition distribution was insensitive to combustion scale. Specific mineral interactions were therefore common to all facilities for the coal examined. A detailed description of the combustor, test program, and test results is contained in Section 7 of this report. Additional information on the characterization of the SECV samples is provided in Section 4. (Φ2)

- (14) ***Pyrite Transformations*** The combustion reaction history of pyrite minerals was examined in a PSIT drop tube furnace study. Pure hydrothermal pyrite was ground, sieved, fed to the furnace, collected at various residence times, and examined for morphology and chemical composition. Pyrite was shown to initially lose sulfur to form a porous pyrrhotite, which then melted to form an iron oxy-sulfide melt. As oxidation of the melt proceeded, magnetite crystallization began. Eventually, complete oxidation of the melt produced a crystalline oxide product with a Mössbauer spectrum characteristic of hematite.

Deposition testing at various residence times indicated that pyrite-derived products were prone to deposit whenever a melt phase was present. Measurements and subsequent modeling indicated that the melt phase was present for approximately 80% of the time required for oxidation to crystalline magnetite. These results were discussed in detail in Section 8.3.5 of the Phase 1 Final Report. (Φ1)

- (15) ***Model of Pyrite Transformations*** A kinetic model to describe the chemical transformations of excluded pyrite in a combustion environment was developed. The model demonstrated that oxidation of pyrite was externally diffusion controlled, with the reaction time proportional to (particle diameter)². Measured literature values of pyrite particle combustion temperatures were successfully predicted by the model. As noted above, the model also indicated that nearly 80 percent of the time necessary for complete oxidation of magnetite is spent in a partial or complete molten state. These results were discussed in detail in Section 8.4.2 of the Phase 1 Final Report. (Φ1)

- (16) ***Illite Transformations*** A study of illite transformations, both as an excluded mineral and as inclusions in synthetic char particles, was conducted during Phase 1. At a gas temperature of 1500 K, excluded illite demonstrated no change in particle size. When illite of the same size was included in synthetic char particles, however, coalescence was clearly indicated by both Malvern size measurements and SEM observation. Potassium K-edge XANES spectra of excluded illite particles collected at several residence times were characteristic of melting (i.e., glass formation). This indicated that the elevated particle temperatures associated with carbon oxidation were not essential for illite melting, suggesting that even excluded illite may be sticky upon impaction. No evidence for illite vaporization nor for potassium vaporization from illite was found. Details of this study were presented in Section 8.3.6 of the Phase 1 Final Report. (Φ1)
- (17) ***Clay Mineral Transformations*** The transformations of excluded kaolinite, montmorillonite, and nepheline were also examined in a drop-tube furnace study. Neither melting nor gas evolution were evident for either of two kaolinite samples subjected to temperatures of 1650 K. For the excluded montmorillonite, rapid melting resulting in smooth, glassy spheres that were sticky upon impact with deposition surfaces. For the excluded nepheline, which had a considerable potassium-rich aluminosilicate component, neither gas evolution nor melting were observed at gas temperatures up to 1650 K. These results suggest that montmorillonite ash may contribute significantly to deposit initiation, whereas kaolinite and nepheline may not. CCSEM analysis of the nepheline and montmorillonite are described in Section 4 of this report; experimental results are described in Section 7. (Φ2)
- (18) ***Calcium Reactions*** The form of calcium in the parent coal was demonstrated to have little effect on its ability to interact with silicates and form a glass. Experiments conducted with synthetic chars containing quartz inclusions and either (a) dispersed organically associated calcium, or (b) discrete calcium carbonate mineral inclusions, produced identical compositions (XANES spectra) in the ash. The spectra were indicative of a mixture of calcium oxide and calcium silicate glass. Analysis of size-segregated ash samples generated during combustion of low-rank coals also demonstrated existence of calcium oxide and calcium (alumino)silicate phases. Calcium oxide levels decreased with decreasing ash particle size. Because calcium compounds are forming through coalescence of aluminosilicate minerals with calcium compounds, this suggests that only the smallest ash particles have sufficient time to react fully with aluminosilicates before the char particle burns out. Larger ash particles retain a calcium-oxide rich coating. Initial results were discussed in Section 6 of the Phase 1 Final Report; recent work in this area is discussed in Sections 4.5.8 and 6.6.4 of this report. (Φ1,2)
- (19) ***Iron-Aluminosilicate Reactions*** A comparison of Mössbauer and CCSEM analyses for combustion-derived ash revealed that the amount of iron oxide identified by CCSEM was approximately 1/2 of the true value in the ash. This finding suggested that iron oxide was in intimate contact with aluminosilicate ash particles, thus

appearing to the CCSEM as iron aluminosilicates. A detailed high-resolution TEM study of ash from Beulah lignite and Illinois #6 bituminous coals was conducted by UA to determine whether iron was crystallizing out of aluminosilicate glasses during sampling, or whether iron-aluminosilicate coalescence was incomplete. Results indicated that agglomerated but incompletely coalesced iron-aluminosilicate clusters were forming, thus preserving iron in the oxidized state. This suggests that the time scales for pulverized coal combustion are insufficient to allow for complete reaction of iron compounds with aluminosilicate ash particles. Results of this study are presented in Section 6.8 of this report. (Φ2)

- (20) ***Alkali-enhanced Coalescence*** The role of alkali metals in reducing the coalescence time for ash particles was investigated. Synthetic char particles containing uniform, sol-gel produced, spherical silica inclusions with differing levels of potassium were prepared. Combustion experiments conducted with four different chars indicated that the extent of silica coalescence was strongly dependent upon the level of potassium in the coal, with increasing potassium leading to increased silica coalescence. The postulated mechanism was a reduction in silica viscosity through the introduction of a network modifier (potassium), thus increasing coalescence rates. Results are described in detail in Section 5.4.3 of this report. (Φ2)
- (21) ***Ash Particle Stickiness and Deposit Initiation*** The viscosity of individual ash particles was shown to be the important parameter in determining the stickiness of ash particles upon impact with a clean high temperature tube surface. In experiments conducted in a drop tube furnace, soda-lime-silica glass particles were passed through an isothermal zone and accelerated toward a tube surface. By maintaining the tube at the same temperature as the local gas, the temperature of the particles upon impact was known. Bulk gas temperature variations were thus used to explore the effects of viscosity variations on particle adhesion to the target. In these experiments, for the range of particle kinetic energies expected upon inertial impact, particle viscosities in the range of approximately 10^5 to 10^7 Pa·s were sufficient to cause adhesion. Note that this viscosity range is several orders of magnitude higher than the flow viscosities sometimes used to characterize a coal's ash deposition tendency. The results of this study were described in detail in Section 8.3.7 of the Phase 1 Final Report. (Φ1)

Deposition experiments conducted with the coals from Phases 1 and 2 demonstrated a wide range of ash particle stickiness behavior. For the Phase 1 coals, the stickiness of the coal ashes at similar impaction conditions and identical temperature was found to be San Miguel > Beulah, Eagle Butte > Kentucky #11 > Kentucky #9, Upper Freeport, Illinois #6 > Loy Yang. Calcium-rich aluminosilicate ash particles appeared to be the most likely to initiate deposition. Note that this ranking is for collection efficiency - the impaction efficiency or size distribution of the ash particles is not included. The stickiness of all four of the low-ash Phase 2 coals (Gravimelt 7A, Gravimelt 9C, Illinois #6 SOAP, Loy Yang 1953) was significantly lower than any of the Phase 1 U.S. coals at comparable conditions. Only the Loy Yang 2301 produced collection efficiencies as low as the Phase 2 coals (typically < 10% of the

ash at approximately 1500 K). Although low impactation efficiencies do contribute to the apparent lower values for Phase 2 coals, the lack of significant calcium aluminosilicate formation tended to keep absolute stickiness at a low value as well. Thus, ash from these coals was less likely to impact, and less likely to stick upon impactation than ash from "raw" coals.

Deposition tests utilizing Beulah lignite, Loy Yang 1953, and treated Loy Yang 1953 coals were also conducted at the pilot scale facilities at SECV. For the Beulah lignite, short term uncooled probe samples showed iron enrichment in the deposit initial layers, suggesting deposition of molten pyrite-derived species. Longer term and lower temperature deposition probe samples showed a doubling of the Ca/Fe ratio, suggesting calcium aluminosilicate deposition was more important at later times. Compared to Beulah lignite, much smaller deposits were observed during testing of the Loy Yang coal, due to both the lower ash content, smaller ash particle size, and reduced stickiness of the ash particles. Deposits collected from uncooled surfaces were a mixture of iron and silicon phases, suggesting possible silicate deposition. Samples collected from cooled surfaces were sodium sulfate enriched. Addition of aluminum and magnesium additives significantly reduced the amount of deposition for the Loy Yang.

Initial stickiness testing results were described in detail in Section 8.3.7 of the Phase 1 Final Report; additional data and data analysis are presented in Sections 4 and 7 of this report. (Φ 1,2)

- (22) ***Submicron Ash Fume Formation*** The mass fraction of ash found in the submicron mode during combustion of utility grind samples of the seven Phase 1 U.S. coals varied between 0 to 3%. Organically associated species such as sodium and, to a lesser extent, calcium were generally present in the highest concentrations, although for some bituminous coals, all elements were observed. When narrow size and density fractions of the coals were burned, the amount of submicron ash increased to the 1 to 10% range. Vaporization and recondensation of the inorganic constituents was found to be the most probable mechanism for production of the submicron ash. For the beneficiated and low-ash coals considered in Phase 2, a larger fraction of the ash was generally present in the submicron range. Sodium and potassium were generally the dominant species for these submicron ashes.

Details of the initial portion of this study were provided in Sections 6, 7, and 8 of the Phase 1 Final Report. A summary, including recent findings using the beneficiated and low ash coals, is presented in Sections 5, 6 and 7 of this report. (Φ1,2)

- (23) ***Surface Enrichment of Submicron Ash*** Auger electron spectroscopic analysis performed on samples of submicron ash collected after combustion demonstrated surface enrichment in alkali species. Sodium species enrichment was particularly noted. Quenching of the post-combustion gases at various post-combustion residence times demonstrated further enhancement of the alkali coating. Only sodium,

potassium, and calcium were found to be enriched in the submicron ash fume (and in one case only, silicon). Results were described in Section 7 of the Phase 1 Final Report; additional atomic absorption spectroscopic data for composition as a function of ash particle size are presented in Section 6 of this report. (Φ1,2)

- (24) **Sodium Vaporization** The fraction of sodium appearing in the submicron fume was found to correlate with the ratio of organically associated sodium-to-silicate minerals in a given coal. Coals with high sodium to silicon ratios produced submicron ashes containing a high percentage of the total sodium found in the coal. Addition of excluded (extraneous) aluminosilicates to the coal significantly reduced the fraction of sodium found in the submicron size range. The reduced fraction, however, was still greater for the doped coal than for those coals with comparable concentration of aluminosilicates, only in *included* form. This suggests that capture of sodium by external aluminosilicates may be less efficient than capture by aluminosilicate minerals contained within the coal's organic matrix. Modeling results indicated that internal capture is limited by significant mass transfer resistances, and by the inability of aluminosilicates to interact with alkali species after the minerals have undergone extensive coalescence with other minerals. Results are described in Section 6 of this report. (Φ1,2).
- (25) **In-Situ Measurement of Vapor Phase NaCl** In-situ measurements of vapor phase sodium chloride were conducted successfully for the first time, using laser-induced photodissociation and fluorescence (LIPF). In experiments conducted with several program coals, the amount of NaCl present in the post-flame gases at a temperature of approximately 1200 K was related to the amount of chlorine present in the parent coal. Results were described in detail in Section 8.3.8 of the Phase 1 Final Report. (Φ1).
- (26) **Sodium Kinetics Model** A homogeneous gas phase alkali kinetics model was developed, using rate coefficients from the literature, to analyze the time required for formation of molecular sodium species. It was determined that formation of molecular species occurred on a millisecond to ten millisecond time scale, fast compared to the time scales for coal combustion (100 ms to 1 s). Sodium hydroxide and sodium chloride were found to be the major species, with the relative amounts depending upon the chlorine content of the coal. Results were discussed in Section 8.4.1 of the Phase 1 Final Report and are reviewed in Section 6.6 of this report. (Φ1)
- (27) **Potassium Vaporization** Unlike sodium, potassium vaporization did not correlate with the amount of silicates present in a coal. This is because of the large amount of illitic potassium contained in coal minerals, which is of low activity and therefore does not vaporize at combustion temperatures. Only in cases where the illite was smaller than a few microns in size and temperatures were higher than "typical" combustion temperatures (oxygen > 50%) was any potassium vaporization from illite noted. Potassium vaporization did, however, correlate with the amount of sodium

vaporized. Experiments conducted with a bituminous coal and extraneous sodium at coal combustion temperatures demonstrated a 5 to 17-fold increase in potassium vaporization. At lower temperatures (1070 K), chlorine was also necessary for K to displace Na. Results are described in Sections 6.6.4 and 8.3.6 of the Phase 1 Final Report, and Section 6.6.3 of this report. (Φ 1,2)

- (28) **Calcium Vaporization** An experimental study on the origins of calcium found in submicron ash indicated that mineral-bound calcium does not vaporize. In experiments conducted with synthetic chars containing several types of calcium, only organically bound calcium was found to vaporize. Vaporized levels were $< 3\%$ of the calcium at oxygen partial pressures of 0.20 atmosphere; higher oxygen concentrations (and thus higher combustion temperatures) were required before significant Ca vaporization was observed. The presence of sulfur was found to slightly reduce the amount of calcium vaporized, presumably through the formation of calcium sulfide. Modeling the system indicated that calcium vaporization would occur by CO reduction of CaO to Ca, with the reduction kinetics playing an important role at typical combustion temperatures (particle temperatures below 2500 K). Results are discussed in Section 5.3 of this report. (Φ 1,2)
- (29) **Silicon Vaporization** The amount of silicon vaporized from coals and synthetic chars examined in this study was low - typically less than 1% of the total silicon in the fuel. Silicon vaporization was found to depend upon the amount, size, and composition of silica in the coal. Increasing silica concentration, increasing size of silica inclusions, or increasing the fraction of total Si present as aluminosilicates all reduced the amount of silicon vaporized. The presence of sulfur slightly enhanced the vaporization of silicon. Silicon was concluded to vaporize as SiO under all conditions, although the mechanism for formation of SiO varied with temperature. Results are presented in Section 5.3 of this report. (Φ 1,2)
- (30) **Iron Vaporization** Experiments conducted with several coals and synthetic chars indicated that the amount of iron vaporized during combustion was strongly dependent upon the size of the iron (pyrite) inclusions in coal. Under combustion conditions of 1650 K and 20% oxygen, approximately 35% of the iron contained in 1 to 5 μ m pyrite inclusions in synthetic chars vaporized; only 1 to 3% of the iron contained as larger pyrite inclusions in several coals vaporized under identical conditions. No vaporization was noted for a sample of excluded pyrite, indicating that iron vaporization occurs primarily from included pyrite minerals. Modeling indicated that iron vaporization can occur as atomic iron, due to the iron vapor pressure above Fe_{1-x}S melts. Results of this study are presented in Section 5.3 of this report. (Φ 1,2)

Experiments with hydrothermal and synthetic pyrite particles conducted in a laser-heated electrodynamic balance also demonstrated that vaporization of iron from excluded pyrite was unlikely. Mass loss noted at high temperatures was found to be primarily a result of sulfur and "impurities" vaporization, rather than iron. These results were discussed in Section 5.1.4 of the Phase 1 Final Report. (Φ 1).

- (31) ***Mobility of Submicron Ash Agglomerates*** Model titania and silicon aerosols, chosen as being representative of non-coalescing ash aerosols, were produced in a laboratory reactor and structurally characterized. The mobility of these particles was measured as a means of exploring the relationship between agglomerate structure and aerodynamic drag, which may affect deposition. The mobility of these particles was found to depend only on the projected area; shape parameters such as fractal dimension, although variable, did not influence the results. Changes in the fractal dimension with processing conditions were linked to sintering, however, suggesting the possible use of fractal dimension as an indicator for the degree of ash coalescence. These results were discussed in detail in Section 5 of the Phase 1 Final Report. (Φ1)

- (32) ***Trace Metal Transformations*** Illinois #6 and Illinois #6 SOAP coals and their combustion-derived ashes were analyzed in an initial effort to assess the effects of beneficiation on trace element transformations. Coal cleaning significantly reduced the levels of Co and Zn, slightly reduced the levels of As and Se, and had no effect on the levels of Cr and Sb. As, Sb, Zn, and Se were all enriched in the submicron ash for these coals, suggesting at least partial vaporization and recondensation.

Chromium was further analyzed by XAFS spectroscopy to identify the form of this element in the coals and ashes. Several standard materials were also examined. Results indicated that chromium was present exclusively in the less toxic +3 oxidation state. No evidence for the existence of the toxic and carcinogenic +6 form of chromium was found. Results are described in Sections 4 and 7 of this report. (Φ2)

- (33) ***Coal Char Combustion Model*** A model for the prediction of char particle combustion temperatures and burning times was developed. This model differs from previous single particle combustion models in several aspects. First, the oxidation of CO to CO₂ was included. Second, intrinsic kinetics were included to permit evaluation of particle temperatures and combustion rates below 2200 K (the point at which intrinsic kinetics begin to play a role). Third, the increase in gas boundary layer thermal conductivity due to the dissociation of oxygen at high temperatures was included. Fourth, and finally, temperatures were evaluated on a time-weighted average basis to avoid biasing the results toward the highest (initial) temperatures. With these modifications, the model accurately predicted experimentally determined single particle temperatures reported in the literature, and was subsequently used to predict combustion temperatures for experiments conducted at MIT in this program. A description of the development and evaluation of this model can be found in Section 5.3.1 of this report. (Φ2)

- (34) ***Iron-Aluminosilicate Interaction Model*** A model for predicting the partitioning of iron between glassy and crystalline phases was developed. The model, which was fit to UA laboratory data, uses as input parameters the mass fractions of iron and aluminosilicate minerals in the coal, the size distributions of these minerals, the gas temperature profile, and the gas oxygen concentration. Initial simulations conducted

with this model suggested that significant iron-glass formation does not begin until several hundred milliseconds after injection of the coal into a furnace. This model is discussed in Section 6.9 of this report. (Φ2)

- (35) **Char Fragmentation Model** A Monte Carlo model of char fragmentation, based upon percolation techniques, was developed to study the role of macroporosity. Char particles were defined in a discretized, three-dimensional space. Variable sizes and amounts of mineral inclusions, and various degrees of curvature (spherical v. planar surfaces) were considered in these simulations. The model successfully predicted the experimentally observed breakup of char particles near burnout for macroporous chars. Analytical expressions were developed for the ash particle size distribution by considering a surface ash particle scavenging mineral inclusions as the char surface recedes. Using this approach, the competition between surface ash coalescence and char fragmentation could be analyzed. It was found that surface coalescence was only significant during the initial 10% and final 10% of burnout; during the intervening stage, most ash growth occurred through internal minerals becoming subsumed by surface ash particles.

In the presence of macroporosity, the model demonstrated that the development of a bimodal ash particle size distribution was inevitable. Results were found to be self-similar, however; i.e., the peaks in the distribution occurred at a constant value of s/S , the ratio of the ash size to mean or average ash particle size, of 0.01.

In order to overcome the modeling difficulties caused by the discrete spatial representation of char in the model, an additional model was developed employing the effect of char fragmentation in an ad hoc manner, i.e., with an assumption that receding ash particles get separated from the char as they encounter pores. The results of the additional modeling work verified most of the findings from the char fragmentation modeling work.

The development and use of the fragmentation models is described in detail in Section 6 of the Phase 1 Final Report and in Section 5.4 of this report. (Φ1,2)

- (36) **Equilibrium Modeling** Equilibrium modeling of non-ideal solutions was achieved through modifications to the SOLGASMIX equilibrium code. Calculations with this model indicated that sodium (or potassium by analogy) was unlikely to vaporize because of low activity in silicate melts, consistent with the experimental findings of this program. The results of these calculations were described in Section 8.4.3 of the Phase 1 Final Report. (Φ1)

Equilibrium modeling was also used to assess alkali partitioning under post-combustion conditions. Sodium sulfate was not expected to be a major vapor phase species, but was shown to be a dominant condensed phase species at temperatures below approximately 1000 K (depending upon the system chemistry). Elemental sodium vapor was only important under either reducing conditions, or at temperatures

above 1600 K (or higher; again, dependent upon system chemistry). The results of alkali system equilibrium calculations are discussed in Section 8.3.8 of the Phase 1 Final Report and in Section 6.6.1 of this report. (Φ1,2)

- (37) ***Mineral Redistribution Model*** A Monte Carlo mineral redistribution model was developed to investigate the variation of mineral content and composition from coal particle to coal particle. The model randomly distributes the various size and composition classes of minerals, measured by CCSEM, among several coal particle size bins. Once all of the measured mineral matter has been distributed, density classification is performed mathematically. Agreement between predicted and measured density fractionation results was noted for Beulah lignite, Upper Freeport, and Kentucky # 11 coals. Results were described in detail in Section 6.5.6 of the Phase 1 Final Report. (Φ1)
- (38) ***Engineering Model to Predict Ash Particle Size and Composition Distributions*** A major "deliverable" of this project was the development of a model capable of describing the *distribution* of ash particle sizes and chemical compositions resulting from the combustion of pulverized coal. This model was developed during Phase 2 of this program by synthesizing the mineral redistribution model, conclusions and scaling laws derived from the char fragmentation models, and scaling laws and descriptions of mineral coalescence derived from the fundamental experiments conducted in this program.

The Engineering Model (EM) first simulates the distribution of minerals in pulverized coal by distributing them with a streamlined version of the mineral redistribution model. A composite model using Monte-Carlo methods and Poisson statistics was developed to minimize the computational effort required to distribute the various minerals among the wide range of coal particle sizes. This method requires less computer memory and shorter run times while providing better statistics and handling a wider range of coal and mineral sizes than a pure Monte Carlo approach. Random placement of the minerals within the coal particles was done discretely (i.e., by pure Monte-Carlo) when the average number of mineral particles per coal particle was small. When the average number was large, Poisson statistics were used to determine the number of mineral particles assigned to each coal particle.

In addition to modeling the initial ensemble of coal and minerals, the combustion transformations (mineral coalescence and fragmentation, char fragmentation) were also modeled to predict ash formation. Depending upon the initial distribution of minerals within coal, either full coalescence, partial coalescence, or no coalescence scenarios could be evaluated. Coalescence is governed by the mineral particle encounter probabilities determined using arguments drawn from the kinetic theory of gases. Coalescence of organically associated species such as calcium can also be included, by assigning one or more of the mineral types to these species. Char fragmentation, defined as an interruption to mineral coalescence, takes into account

cenosphere formation and the coalescence of different sized mineral particles as the char particle shrinks during combustion.

A range of US bituminous and lignitic coals was examined to provide a comprehensive description of ash formation during pulverized coal combustion. A methodology was also developed to compare the ash distribution with the measured distributions of ash size and composition, to directly assess the degree of mineral coalescence and char fragmentation. For the limiting case of full coalescence, ash particle size distributions were in good agreement with experimental data. More importantly, the ash particle *composition* distributions were in good agreement with experimental data, demonstrating the ability of the model to predict information critical to the prediction of deposition, that is, the size-resolved chemical composition of individual ash particles.

The development and use of the Engineering Model is described in Section 7.9 of this report. (Φ2)

- (39) ***Graduate Student Doctoral Theses*** Several graduate students were supported either wholly or in part by this program. Their theses have made a significant contribution to the literature on ash formation and growth. An alphabetical listing of the works receiving significant financial support from this program follows.

Bool, L.E., "The Partitioning of Iron During the Combustion of Pulverized Coal,," in progress; Ph.D. Thesis to be submitted to the Department of Chemical Engineering, University of Arizona, Tucson AZ, expected completion May (1993).

Gallagher, N.B., "Alkali Metal Partitioning in a Pulverized Coal Combustion Environment," Ph.D. Thesis submitted to the Department of Chemical Engineering, University of Arizona, Tucson AZ (1992).

Graham, K.A., "Submicron Ash Formation and Interactions with Sulfur Oxides During Pulverized Coal Combustion," Ph.D. Thesis submitted to the Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge MA (1991).

Kang, S.G., "Fundamental Studies of Mineral Matter Transformations During Pulverized Coal Combustion: Residual Ash Formation," Ph.D. Thesis submitted to the Department of Chemical Engineering, Massachusetts Institute of Technology, Cambridge MA (1991).

Rojak, S.N., "Aerosol Dynamics of Agglomerates," Ph.D. Thesis submitted to the Department of Environmental Engineering Science, California Institute of Technology, Pasadena CA (1991).

Shah, A., "Characterization of Mineral Matter and Ash Samples Using Advanced Analytical Techniques (tentative title)," in progress; Ph.D. Thesis to be submitted to the Department of Chemical Engineering, University of Kentucky, Lexington KY, expected completion May (1993).

Wong, B. A., "The Oxidation of Individually Levitated Char Particles," Ph.D. Thesis submitted to the Department of Environmental Engineering Science, California Institute of Technology, Pasadena CA (1991).

(40) *Publications and Presentations*

Boni, A.A., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Huffman, G.P., Huggins, F.E., Helble, J.J., and Srinivasachar, S. (1991), "Transformation of Inorganic Coal Constituents in Combustion Systems," PSI-1024/SR-560, Seventh Annual Coal Preparation, Utilization, and Environmental Control Contractors Conference.

Boni, A.A., Helble, J.J., and Srinivasachar, S. (1990), "Effect of Mineral Matter on Power Plant Performance - Status and Future Prospects," presented at EPRI Conference on the Effects of Coal Quality in Power Plant Performance, St. Louis, September 19-21.

Boni, A.A., Helble, J.J., Srinivasachar, S., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Flagan, R.C., Bryers, R.W., Huffman, G.P., and Huggins, F.E., (1990), "Transformations of Inorganic Coal Constituents in Combustion Systems," Phase I Final Report under DOE contract DE-AC22-86PC90751. NTIS document number DOE/PC/90751-T4-90014467 and -90014468.

Boni, A.A., Helble, J.J., Srinivasachar, S., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Flagan, R.C., Bryers, R.W., Huffman, G.P., and Huggins, F.E., (1990), "Transformations of Inorganic Coal Constituents in Combustion Systems," PSI-1024/SR-513, AR&TD Contractors Meeting, Pittsburgh (September).

Boni, A.A., Johnson, S.A., Helble, J.J., and Srinivasachar, S. (1990), "Mineral Matter Transformations During Coal Combustion: Fundamental Results and Relevance to Deposition," presented at ASME Ash Deposit and Corrosion Research Committee Seminar on Fireside Fouling Problems, Provo, UT.

Boni, A.A., Helble, J.J., and Srinivasachar, S. (1989), "Impact of Coal Minerals on Boiler Slagging and Fouling," presented at the Workshop on Coal-Fired Boilers, Bethlehem, PA (June).

Boni, A.A., Flagan, R.C., Bryers, R.W., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Huggins, F.E., Huffman, G.P., Helble, J.J., and

Srinivasachar, S. (1989), "Transformations of Inorganic Coal Constituents in Combustion Systems," AR&TD Contractors Meeting, Proceedings, p. 175.

Boni, A.A., Flagan, R.C., Bryers, R.W., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Huggins, F.E., Huffman, G.P., Helble, J.J., and Srinivasachar, S. (1988), "Transformations of Inorganic Coal Constituents in Combustion Systems," AR&TD Contractors Meeting, Proceedings, p. 287.

Boni, A.A., Flagan, R.C., Bryers, R.W., Sarofim, A.F., Beér, J.M., Peterson, T.W., Wendt, J.O.L., Huggins, F.E., Huffman, G.P., Helble, J.J., and Srinivasachar, S. (1987), "Transformations of Inorganic Coal Constituents in Combustion Systems," AR&TD Contractors Meeting, Proceedings, p. 497.

Charon, O., Sarofim, A.F., and Beer, J.M., "Distribution of Mineral Matter in Pulverized Coal," Prog. Energy Combust. Sci., 16 (4), 319 (1990).

Gallagher, N.B., Bool, L.E., and Wendt, J.O.L. (1991), "Modeling of Alkali/Silicate Interactions During Pulverized Coal Combustion," ACS Division of Fuel Chem. Preprints, 36(1), 181.

Gallagher, N.B., Bool, L.E., Wendt, J.O.L., and Peterson, T.W. (1990), "Alkali Metal Partitioning in Ash from Pulverized Coal Combustion," Combustion Science and Technology, 74, 211.

Graham, K.A., Helble, J.J., Kang, S-G., Sarofim, A.F., and Beer, J.M. (1990), "Mechanisms of the Transformation of Mineral Matter to Ash in Coal and Model Chars," in Mineral Matter and Ash Deposition From Coal, Proc. Engineering Foundation Conf. (eds., K.S. Vorres and R.W. Bryers), United Engineering Trustees, New York, p. 165.

Helble, J.J., Srinivasachar, S., Boni, A.A., Charon, O., and Modestino, A., (1992), "Measurement and Modeling of Vapor Phase NaCl Formed During Pulverized Coal Combustion," Comb. Sci. and Tech., 18, 193.

Helble, J.J., Huggins, F.E., Senior, C.L., Srinivasachar, S., Shah, N., and Huffman, G.P. (1992), "The Fate of Chromium During Pulverized Coal Combustion," Proc. Ninth Annual (Int'l) Pittsburgh Coal Conference.

Helble, J.J., Srinivasachar, S., Kang, S.G., Wilemski, G., Boni, A.A., Sarofim, A.F., Beér, J.M., Huffman, G.P., Huggins, F.E., Peterson, T.W., and Wendt, J.O.L. (1992), "Transformations of Inorganic Coal Constituents in Combustion Systems," Eighth Annual Coal Preparation, Utilization, and Environmental Control Contractors Conference, p. 89.

Helble, J.J., Moore, J.W., and Domazetis, G. (1992), "The Evolution of Ash Particle Chemistry During Pulverized Coal Combustion," presented at the poster session of the Twenty-Fourth Symposium (Int'l) on Combustion, Sydney (July).

Helble, J.J., Srinivasachar, S., Senior, C.L., Huggins, F.E., Shah, N., and Huffman, G.P. (1991), "Effect of Coal Cleaning on the Partitioning of Trace Elements in Aerosols Generated During PC Combustion," presented at the 1991 Pittsburgh Coal Conf., Pittsburgh (October).

Helble, J.J. and Srinivasachar, S. (1991) "The Effect of Coal Cleaning on the Partitioning of Trace Elements in Aerosols Generated During Pulverized Coal Combustion," AAAR Annual Meeting, Traverse City, MI (October).

Helble, J.J., Srinivasachar, S., Boni, A.A., Kang, S.G., Graham, K.A., Sarofim, A.F., Beer, J.M., Gallagher, N.B., Bool, L.E. Peterson, T.W., Wendt, J.O.L., Shah, N., Huggins, F.E., and Huffman, G.P. (1991), "Mechanisms of Ash Evolution - A Fundamental Study. Part I: Low Rank Coals and the Role of Calcium," Proc. Engineering Foundation Conference on Inorganic Transformations and Ash Deposition During Combustion, p. 209.

Helble, J.J., Srinivasachar, S., Boni, A.A., Kang, S.G., Graham, K.A., Sarofim, A.F., Beer, J.M., Gallagher, N.B., Bool, L.E. Peterson, T.W., Wendt, J.O.L., Shah, N., Huggins, F.E., and Huffman, G.P. (1991), "Mechanisms of Ash Evolution - A Fundamental Study. Part II: Bituminous Coals and the Role of Iron and Potassium," Proc. Engineering Foundation Conference on Inorganic Transformations and Ash Deposition During Combustion, p. 229.

Helble, J.J., Srinivasachar, S., and Boni, A.A. (1991), "The Behavior of Clay Minerals Under Combustion Conditions," Presented at the 201st National Spring ACS Meeting, Atlanta, GA (April). ACS Division Fuel Chemistry Preprints, 36(1), 173.

Helble, J.J., Srinivasachar, S., and Boni, A.A. (1990), "A Fundamental Study of Ash Particle Adhesion," Proc. Seventh Annual International Pittsburgh Coal Conference, p. 52.

Helble, J.J., Srinivasachar, S., and Boni, A.A. (1990), "Factors Influencing the Transformation of Minerals During Pulverized Coal Combustion," Prog. Energy and Comb. Sci., 16, 267.

Helble, J.J., Srinivasachar, S., and Boni, A.A. (1990), "An Overview of the Fundamentals of Mineral Transformations and Implications for Deposition," invited paper, Proc. First Australian Workshop on Ash Deposition, Brisbane, June.

Helble, J.J., Srinivasachar, S., and Boni, A.A. (1989), "Factors Influencing the Transformation of Minerals During Pulverized Coal Combustion," presented at 198th ACS National Meeting (April).

Helble, J.J., Srinivasachar, S., Boni, A.A., Kang, S-G., Sarofim, A.F., Beer, J.M., Shah, N., Huggins, F.E., Huffman, G.P., Peterson, T.W., and Wendt, J.O.L. (1989), "Effects of Combustion Scale on Fundamental Mineral Transformations for Selected U.S. Coals," Proceedings of the Sixth Annual Pittsburgh Coal Conference, Vol. 1, p. 81.

Helble, J.J., Srinivasachar, S., Katz, C.B., and Boni, A.A. (1989), "Mineral Transformations as a Key to Understanding Deposition During Low-Rank Coal Combustion," Proc. Fifteenth Biennial Low-Rank Fuels Symposium.

Helble, J.J., Srinivasachar, S., Katz, C.B., and Boni, A.A. (1988), "Transformation and Adhesion of Minerals During Pulverized Coal Combustion," presented at the poster session of the Twenty-Second Symposium (Int'l) on Combustion, Seattle (August).

Huffman, G.P., Huggins, F.E., and Shah, N. (1990), "Behavior of Basic Elements During Coal Combustion," Prog. Energy Combust. Sci., 16, 243.

Huffman, G.P., Huggins, F.E., and Shah, N. (1990), "XAFS Spectroscopy: A New Technique for Investigating Impurity Elements in Coal That Control Slagging and Fouling Behavior," in Mineral Matter and Ash Deposition From Coal, Proceedings, Engineering Foundation Conference (eds. K.S. Vorres and R.W. Bryers), United Engineering Trustees, New York, p. 63.

Huffman, G.P., Huggins, F.E., and Shah, N. (1990), "XAFS Spectroscopy Studies of Critical Elements in Coal and Coal Derivatives," Proc. Conf. Coal Spectroscopy, (ed. H.L.C. Meuzelaar).

Huffman, G.P., Huggins, F.E., and Shah, N. (1989), "Behavior of Basic Elements During Coal Combustion," presented at 198th ACS National Meeting.

Kang, S.G., Sarofim, A.F., and Beér, J.M. (1992), "Effect of Char Structures on Residual Ash Formation During Pulverized Coal Combustion," Proc. Twenty-Fourth Symposium (Int'l) on Combustion, The Combustion Institute (in press).

Kang, S.G., Kerstein, A.R., Helble, J.J., and Sarofim, A.F. (1990), "Simulation of Residual Ash Formation During Pulverized Coal Combustion," Aerosol Science and Tech., 13, 401.

Kang, S-G., Charon, O., Sarofim, A.F. and Beer, J.M. (1989), "Factors Controlling Residual Ash PSD," Proceedings of the Sixth Annual International Pittsburgh Coal Conference, p. 74.

Kang, S.G., Helble, J.J., Sarofim, A.F., and Beér, J.M. (1988), "Time Resolved Evolution of Fly Ash During Pulverized Coal Combustion," Proc. Twenty-Second Symposium (Int'l) on Combustion, The Combustion Institute, p. 231.

Levendis, Y.A., Nam, S.W., Loewenberg, M., Flagan, R.C. and Gavalas, G.R. (1989), "Catalysis of the Combustion of Carbonaceous Particles by Various Forms of Calcium Additives," J. Energy and Fuels, 3, 28.

Rogak, S.N. and Flagan, R.C. (1990), "Stokes Drag on Self-Similar Clusters of Spheres," J. Colloid and Interface Science, 134, 206.

Sarofim, A.F. (1990), "Fundamental Study of Ash Formation and Mineral Matter Transformations," presented at Finnish/Swedish Flame Days, Turkku, Finland (September).

Scotto, M., Bassham, E., Wendt, J.O.L., and Peterson, T.W. (1990), "Inorganic Aerosol Behavior in Beulah Lignites: Influence of Temperature Quench Rate," in Mineral Matter and Ash Deposition from Coal, Proc. Engineering Foundation Conference (eds. K.S. Vorres and R.W. Bryers), United Engineering Trustees, New York, p. 187.

Shah, N., Huffman, G.P., Huggins, F.E., and Shah, A. (1991), "Graphical Representation of CCSEM Data for Coal Minerals and Ash Particles," ACS Div. of Fuel Chem. Preprints, 36(1), 165.

Shah, N., Huffman, G.P., Huggins, F.E., and Shah, A. (1991), "Graphical Representation of CCSEM Data for Coal Data for Coal Minerals and Ash Particles," Proceedings, Engineering Foundation Conference on Inorganic Transformations and Ash Deposition During Combustion, p. 179.

Shah, N., Huffman, G.P., Huggins, F.E., and Shah, A. (1991), "Reaction of Calcium and Alkali Elements with Aluminosilicates and Quartz During Coal Combustion," Proceedings of the International Conference on Coal Science in Newcastle, England, September 16-20.

Shah, A., Huggins, F.E., Shah, A., and Huffman, G.P. (1991), "The Form of Occurrence of Basic Elements in Coal and Their Behavior During Combustion," ACS Div. of Fuel Chem. Preprints, 35(3), 653.

Srinivasachar, S., Helble, J.J., and Boni, A.A. (1990), "An Experimental Study of the Inertial Deposition of Ash Under Coal Combustion Conditions," Proc. Twenty-

Third Symposium (Int'l) on Combustion, The Combustion Institute, Pittsburgh, p. 1305.

Srinivasachar, S., Helble, J.J., and Boni, A.A. (1990), "Mineral Behavior During Coal Combustion -- 1. Pyrite Transformations," Prog. Energy and Comb. Sci., **16**, 281.

Srinivasachar, S., Helble, J.J., Boni, A.A., Huffman, G.P., Huggins, F.E., and Shah, N. (1990), "Mineral Behavior During Coal Combustion -- 2. Illite Transformations," Prog. Energy and Comb. Sci., **16**, 293.

Srinivasachar, S., Helble, J.J., Ham, D., and Domazetis, G. (1990), "A Kinetic Description of Alkali Transformations in Combustion Systems," Prog. Energy and Comb. Sci., **16**, 303.

Srinivasachar, S., Helble, J.J., Katz, C.B., and Boni, A.A. (1990), "Transformations and Adhesion of Minerals During Pulverized Coal Combustion," in Mineral Matter and Ash Deposition From Coal, Proc. Engineering Foundation Conference (eds. K.S. Vorres and R.W. Bryers), United Engineering Trustees, New York, p. 201.

Srinivasachar, S., Helble, J.J., and Boni, A.A. (1989), "Mineral Behavior During Coal Combustion -- Pyrite Transformations," presented at 198th ACS National Meeting (April).

Srinivasachar, S., Helble, J.J., Boni, A.A., Huffman, G.P., Huggins, F.E., and Shah, N. (1989), "Mineral Behavior During Coal Combustion -- 2. Illite Transformations," presented at 198th ACS National Meeting (April).

Srinivasachar, S., Helble, J.J., Ham, D., and Domazetis, G. (1989), "A Kinetic Description of Alkali Transformations in Combustion Systems," presented at 198th ACS National Meeting (April).

Wilemski, G., Srinivasachar, S., and Sarofim, A.F. (1991), "Modeling of Mineral Matter Redistributions and Ash Formation in Pulverized Coal Combustion," Proc. Engineering Foundation Conference on Inorganic Transformations and Ash Deposition During Combustion, p. 545.

2. INTRODUCTION AND OVERVIEW OF PROGRAM TASKS

This project consists of an integrated series of experimental and modeling tasks performed by PSI Technology Company (PSIT) and three subcontractors (identified below) to achieve the project objectives. Additional work was conducted jointly with the University of North Dakota Energy and Environmental Research Center (UNDEERC) and the State Electricity Commission of Victoria, Australia (SECV) through cooperative agreements. Important elements of this work included coal and ash characterization using advanced analytical techniques, testing in small scale furnaces, testing in moderate to large-pilot scale units, adaptation of fundamental submodels developed previously to beneficiated coal systems, and integration of these submodels and experimental findings into an engineering model used to predict ash particle composition and size distributions. A breakdown of the work performed in each task is presented below. The relationship among all groups is summarized at the end of this section in Figure 2-1.

Task 1 - Program Planning, Management, Reporting, and Peer Review

This task, performed by PSIT, consists of: (1) preparation and annual updating of a Program Plan; (2) overall coordination, management, and integration of the subcontracts and project results; (3) preparation of project monthly reports; (4) integration and final preparation of project quarterly reports; and (5) conduct of semi-annual peer review and project coordination meetings of the project Principal Investigators.

Task 2 - Coal Selection, Preparation, and Characterization

This task was performed by PSIT using the guidelines for mineralogy-based coal selection developed by Foster Wheeler Development Corporation (FWDC) during the first phase of this project. Several parent and beneficiated coals were selected to permit an experimental determination of beneficiation related variables on inorganic transformations during combustion. Emphasis was placed on obtaining both eastern and western coals, cleaned with currently accepted and advanced beneficiation strategies. Coals were acquired by PSIT, pulverized as necessary by an independent contractor on a purchase order basis, and shipped to the various investigators.

Task 3 - Advanced Techniques for Coal and Mineral Characterization

The University of Kentucky (UKY) applied advanced analytical techniques to determine the form, size, and associations of the coal minerals and the resulting ash particles. Work performed in this broad area was broken down into three subtasks. Under Subtask 3.1, UKY worked with other research groups to make improvements in the computer controlled scanning electron microscopy (CCSEM) technique. Under Subtask 3.2, UKY applied CCSEM, Mössbauer spectroscopy, and x-ray absorption fine structure analysis (XAFS) to analyze the mineral forms in the parent coals and the resulting ash products. Under Subtask 3.3, UKY developed an in-situ XAFS capability at the Brookhaven National Laboratories (BNL) Light Source, to be used to determine the associations of inorganic

species in ash particles and initial sticky particle layers without the complications posed by quenching and extractive sampling.

Task 4 - Fundamental Studies of Selected Ash Vaporization, Nucleation, Condensation, and Coagulation Phenomena

Task 4, performed by PSIT, involves thermochemical modeling of the inorganic species expected to be present in the parent coal particles, the beneficiated coal particles, and the final ash particles at various combustion conditions.

Task 5 - Fundamental Studies of Mineral Matter Vaporization and Residual Ash Formation

Experimental and modeling studies were conducted at the Massachusetts Institute of Technology (MIT) on two Subtasks. Under Subtask 5.1, drop tube furnace combustion experiments were conducted with parent coals, beneficiated coals, and model chars to assess the importance of the various mechanisms which control residual ash formation. Emphasis was placed on the expected increasing importance of char fragmentation in shaping the distribution, both experimentally and through adaptation of the percolative fragmentation model developed in the first phase of this project. In Subtask 5.2, the extent of vaporization of inorganic species contained in the parent and beneficiated coals was examined experimentally. Vaporization models developed previously were utilized to interpret results from beneficiated systems.

Task 6 - Pulverized Coal Combustion Studies of Ash Enrichment by Volatiles

The objectives of this task, performed at the University of Arizona (UA) self-sustained reactor facility, were to determine the different fume amounts, compositions, and structures resulting from various beneficiation processes. Mechanistic descriptions of the size and surface composition of the submicron fume formed during combustion were developed. Testing occurred on selected parent and cleaned coals, chosen subsequent to initial screening in the PSIT reactor facility. As part of this effort, the size of the residual ash particles was measured in-situ using an optical single particle measuring instrument provided by PSIT. A model capable of describing the general ash particle size distribution including the effects of fume formation and char fragmentation will also be developed.

Task 7 - Idealized Combustion Determination of Ash Particle Formation and Surface Stickiness

In this task, PSIT employed an idealized combustion system to determine ash particle size and composition distributions for comparison with results obtained at MIT and UA. Emphasis was placed on quantifying the amount of fume, and the amount and chemical composition of ash generated from the various beneficiated coals. Particle stickiness as it pertains to inertial impaction and thermophoretic deposition was addressed. Particle size was analyzed by several means as part of the task, including CCSEM, laser diffraction, and aerodynamic impaction. In addition, the combustor portion of an in-situ XAFS cell was

designed and constructed. Experiments utilizing this cell will be conducted with UKY and BNL at the BNL Light Source to determine ash composition and sticky particle composition in-situ.

Task 8 - Model Development and Integration

In this task, PSIT synthesized the mineral redistribution, char particle fragmentation, and mineral transformation models developed under the various tasks into an overall ash formation model. The result of this synthesis is an engineering model capable of describing the size and, more importantly, the chemical composition of residual ash generated during pulverized coal combustion and the quantity and composition of the ash fume. The information provided by this model can be used to assess the benefits of coal cleaning through a parametric study of ash properties resulting from selective mineral removal.

FIGURE 2-1. - Phase II program structure.

SECTION 3

TASK 2

COAL SELECTION, PREPARATION, AND CHARACTERIZATION (PSIT)

3. TASK 2 - COAL SELECTION, PREPARATION, AND CHARACTERIZATION (PSIT)

During Phase II of this program, efforts focused on developing an understanding of the transformations of inorganic species during combustion of beneficiated coals. Both chemically and physically beneficiated coals were considered, providing a range of ash contents and compositions for study. Coals and cleaning processes were selected to cover the current state of beneficiation technology, and to provide a comparison with the "parent" coals selected for study in Phase I of this program. In this section of the report, the characterization of the Phase II coals is described. Selected data from Phase I coals, acquired and characterized by R.W. Bryers of Foster Wheeler Development Co., are also presented for comparison.

3.1 Background

In the initial phase of the program, emphasis was placed on the selection of coals containing minerals and mineral combinations known to contribute to ash deposition in utility boilers. Four bituminous coals (Kentucky #9, Kentucky #11, Upper Freeport, and Illinois #6), one sub-bituminous coal (Eagle Butte), and two lignites (San Miguel - Texas and Beulah - North Dakota) were selected for study. Samples of each of these coals were acquired, pulverized, riffled, analyzed, and distributed to each of the Phase I subtask Principal Investigators at the start of the program. Loy Yang 2301 brown coal, provided by the State Electricity Commission of Victoria Australia, was also examined by several of the subtask teams. For the seven U.S. coals, special attention was paid to characterization and distribution to ensure that each subtask principal investigator received an *identical* coal sample. Barrels of coal shipped to each investigator were analyzed for ultimate, proximate, and ash chemistry as a quality control check. The acquisition, characterization, and analysis of these eight program coals was described in detail in the Phase I Final Report, "Transformations of Inorganic Coal Constituents in Combustion Systems," submitted by PSI Technology Co. to DOE/PETC in March 1990 (Boni et al., 1990).

At the conclusion of the first 3-year portion of this program, it was clear that coal mineralogy played an important role in determining the size and chemical composition of combustion-generated ash particles. Coal mineralogy in this context is meant to include not just coal minerals, but also those inorganic species generally defined as "organically bound species" as shown in Figure 3-1. Coal mineralogy was expected to play an equally important role in determining ash formation during the combustion of beneficiated coals.

Differences in the dominant ash formation pathways may arise, however, because of changes in mineralogy induced by beneficiation. As summarized in Table 3.1, combustion effects that are unimportant during the combustion of "parent" coals may become dominant during the combustion of cleaned coals. For example, the fragmentation of large pyrite and calcite minerals is an important aspect of ash formation for parent coals. It should be unimportant during combustion of beneficiated coals, however, because coal cleaning generally removes the dense coal particles that contain the large pyrite minerals. Another example is char fragmentation. Although not a primary factor in determining ash particle

C-1890

FIGURE 3.1. - Schematic depiction of coal mineralogy.

TABLE 3.1. - Ash formation issues

Issue	Beneficiated Coal	Parent Coal
Characterization	Small minerals. Dispersed inorganics. Included minerals only.	Larger minerals. Dispersed inorganics. Extraneous minerals.
Mineral coalescence	Uncertain	Dominant
Mineral fragmentation	Insignificant	Important for pyrite and calcite
Char fragmentation	May be dominant	Generally second order effect
Ash particle size	Small	Varies, typically greater than mineral size
Ash chemistry	Uncertain	Silicate dominated
Inorganic vaporization	50% possible	Typically 1 to 2%

size and composition for high ash content coals, it is expected to play an increasingly dominant role as coal ash content decreases. At low ash levels, ash can no longer function as a "glue" keeping char particles intact; hence, lower ash may indicate increased char fragmentation and decreased ash particle sizes. Inorganic vaporization may also increase in importance during the combustion of beneficiated coals if the coal cleaning process removes a significant portion of the coal's mineral matter. Because some organically bound inorganics coalesce with minerals during combustion, removal of these minerals eliminates a "sink" for the organically bound species. Increased inorganic species vaporization, resulting in a greater fraction of the ash mass present as a submicron fume, may therefore result.

It is apparent that different beneficiation processes may affect ash formation to different extents. Mild cleaning which only removes pyrite will decrease the importance of mineral fragmentation but should otherwise leave the ash formation pathways unaffected. Deep chemical cleaning, on the other hand, may lead to an increased fraction of vaporized inorganics and to an increased importance of char fragmentation. The acquisition of beneficiated coals containing a range of ash contents and compositions was therefore a high priority in Phase II of this program.

3.2 Coal Selection, Acquisition, and Distribution

The selection of beneficiated coals for this program was coordinated with DOE/PETC and was designed to include a range of fuels which may be fired by U.S. utilities over the next decade. Early in the Phase II program, it was decided that at least one physically beneficiated coal and at least one chemically beneficiated coal should be included. Because of pending Clean Air Act legislation at the onset of Phase II, a decision to include at least one example of a coal blend (blended for sulfur emissions reduction purposes) was also made. After evaluation of the status of several beneficiation processes and an assessment of the quantities of coal that could be procured, the following coals were selected for Phase II testing: 1) physically beneficiated - Illinois #6 spherical oil agglomeration product (SOAP); Illinois #6 parent coal; 2) chemically beneficiated - Kentucky #9 molten caustic leach cleaned, Pittsburgh #8 molten caustic leach cleaned, and Loy Yang 1953 brown coal from SECV (a naturally occurring low-ash coal); 3) coal blend - Kentucky #9/Eagle Butte 30/70 wt% blend, Kentucky #9 parent, and Eagle Butte parent.

Because of either difficulties in acquiring sufficiently large quantities of a uniform fuel or operational difficulties associated with combustion of some of these coals (e.g., high moisture) in the facilities of this program, not all coals were studied by all program Principal Investigators (PI's). The subset of these eight coals studied by each of the Phase II PI's is shown in Table 3.2.

TABLE 3.2. - Coals studied by Phase II principal investigators

Coal Type	PSIT	MIT	University of Arizona
Illinois #6 SOAP	✓		✓
Illinois #6 parent	✓		
Loy Yang 1953	✓	✓	✓
Kentucky #9 MCL	✓	✓	✓
Pittsburgh #8 MCL	✓	✓	
Eagle Butte/Kentucky #9 Blend	✓	✓	✓
Eagle Butte	✓		
Kentucky #9	✓		

3.3 Description and Characterization of Phase I and II Coals

In this section, we describe the preparation or cleaning process employed for each coal. Analytical data for each of these coals and the coals from Phase I of this program are then reported at the end of the section.

3.3.1 Illinois #6 - Spherical Oil Agglomeration (SOAP)

Illinois #6 Spherical Oil Agglomeration Product (SOAP) coal was produced from pulverized coal mined from the Burning Star No. 4 Mine, Perry County, Illinois. The physical beneficiation process, developed by Bechtel National, Inc. with DOE support (Bechtel, 1990), is outlined in Figure 3.2. Briefly, SOAP processing uses heptane at levels of 10 to 30 wt% of the coal as a bridging liquid to enhance coal particle agglomeration in a high shear reactor. High ash content particles are rejected with water during the slurry drying step. The cleaned product is produced in pellet form by adding asphalt as a binder. As described in the Bechtel report, 75 to 90% pyrite rejection can be achieved with this process.

The samples of Illinois #6 used in this program were obtained in dried form from ABB/Combustion Engineering, Windsor Locks, CT, where the coal is being evaluated as part of the DOE Program "Combustion Characterization of Beneficiated Coal-Based Fuels" (Hargrove et al., 1991). Analytical data obtained for the PSIT sample of this coal are compared with data for the overall Illinois #6 SOAP sample tested at ABB/CE (Hargrove et al., 1991) in Table 3.3. Analytical data for the Illinois #6 parent coals studied in Phases II (SOAP parent) and I of this program are also shown. Phase II PSIT coal data were obtained by the University of North Dakota Energy and Environmental Research Center (UNDEERC) through a cooperative agreement with DOE. Phase I data were taken from the PSIT Phase I Final Report (Boni et al., 1990). All values are reported on a dry basis (moisture levels in

FIGURE 3.2. - Overview of SOAP cleaning process.

TABLE 3-3. - Illinois #6 SOAP and parent coal analysis

	Phase I	Phase II		
	Illinois #6	Parent Illinois #6	PSIT SOAP	CE SOAP
Proximate (wt%)				
Fixed carbon	48.6	51.5	55.5	52.8
Volatile matter	41.4	39.0	40.9	42.9
Ash	9.9	9.4	3.6	4.3
Ultimate (dry; wt%)				
C	69.1	68.3	75.3	75.7
H	5.3	4.9	5.3	5.8
N	1.6	1.2	1.4	1.5
S	4.3	3.3	2.9	2.8
O	9.8	12.9	11.4	9.9
Ash	9.9	9.4	3.6	4.3
Ash composition (wt%)				
SiO ₂	46.1	50.6	39.0	40.2
Al ₂ O ₃	18.0	21.6	18.6	19.9
TiO ₂	0.9	0.9	2.7	2.5
Fe ₂ O ₃	20.5	18.4	27.1	25.6
CaO	5.3	2.1	3.6	3.4
MgO	0.6	1.2	1.4	1.4
Na ₂ O	1.3	0.5	1.4	1.6
K ₂ O	2.1	2.1	2.4	2.4
SO ₃	4.4	2.2	3.5	2.0
P ₂ O ₅	0.1	0.0	0.2	0.2

the PSIT Phase II samples were: parent, 11.1%; SOAP, 23.2%. Moisture levels for the ABB/CE sample were not reported). As expected, the PSIT sub-sample was similar to the Illinois #6 SOAP sample studied at ABB/CE. Beneficiation reduced the ash content of the coal to less than 40% of its original value. Based upon the ash analysis in Table 3.3, aluminosilicates and perhaps quartz were selectively reduced, while increased iron concentrations suggest that pyrite was not removed as efficiently. CCSEM analysis (see Subsections 3.5 and 4 and Tables 4-7 and 4-8) suggested that pyrite levels were reduced, but overall iron concentrations were unaffected. This may reflect oxidation of the pyrite during beneficiation. CCSEM concentration data were qualitatively consistent with the bulk ash

data. Silicon concentrations as a function of the total coal minerals were lower in the SOAP than in the parent. Iron concentrations were comparable. Note that elemental concentrations in Tables 4-7 and 4-8 are on an atom percent basis.

Coal particle size distributions for the Illinois #6 parent and SOAP coals were also determined. The coals were analyzed using a Malvern Instruments particle sizer at UNDEERC. Results are presented in Tables 3-4 and 3-5. A much broader coal particle size distribution (psd) was observed for the parent coal. The psd of the parent Illinois #6 is comparable to that of the Illinois #6 examined in Phase I of this program for particles $\geq 40 \mu\text{m}$ (Boni et al., 1990). For smaller sizes, the distribution of the SOAP parent Illinois #6 is finer (i.e., more coal volume $< 20 \mu\text{m}$ in diameter).

TABLE 3-4. - Malvern PSD - Illinois #6 Parent

Size (μm)	%		Size (μm)	%	
	Under	In-band		Under	In-band
188.0	100.0	0.0	17.7	40.2	4.1
162.0	100.0	0.2	15.3	36.1	3.9
140.0	99.8	0.7	13.2	32.2	3.6
121.0	99.1	1.6	11.4	28.7	3.5
104.0	97.5	2.8	9.8	25.1	3.5
89.9	94.7	4.3	8.5	21.6	3.3
77.5	90.4	5.4	7.3	18.3	3.0
66.9	85.0	5.9	6.3	15.2	2.8
57.7	79.1	5.8	5.4	12.5	3.1
49.8	73.3	5.5	4.7	9.4	3.5
42.9	67.8	5.0	4.1	5.9	2.8
37.1	62.9	4.8	3.5	3.1	1.3
32.0	58.1	4.6	3.0	1.7	0.5
27.6	53.5	4.4	2.6	1.2	0.4
23.8	49.1	4.5	2.2	0.8	0.3
20.5	44.6	4.4	1.9	0.5	

$D(v,0.5) = 24.5 \mu\text{m}$
 $D(v,0.9) = 76.6 \mu\text{m}$
 $D(v,0.1) = 4.8 \mu\text{m}$
 $D(4,3) = 32.7 \mu\text{m}$
 $D(3,2) = 14.0 \mu\text{m}$
Span = 2.9

3.3.2 Kentucky #9 and Pittsburgh #8 - Molten Caustic Leach (Gravimelt)

Samples of chemically beneficiated coal prepared from Kentucky #9 and Pittsburgh #8 bituminous coals were also considered during Phase II of this program. These samples were prepared by the "Gravimelt" molten caustic leaching process developed by TRW. The process used to prepare these samples, illustrated in Figure 3-3 and described generally in Gala et al. (1989), was as follows: samples of the pulverized parent coal were mixed with dry caustic at a coal-to-caustic ratio of 1/2.5. The mixture was fed to a rotary kiln reactor heated to approximately 430°C . Subsequent to dissolution of the minerals in the hot caustic

TABLE 3-5. - Malvern PSD - Illinois #6 SOAP

Size (μm)	%		Size (μm)	%	
	Under	In-band		Under	In-band
188.0	100.0	0.1	17.7	29.0	7.5
162.0	99.9	0.4	15.3	21.5	6.0
140.0	99.5	0.6	13.2	15.5	5.1
121.0	98.9	0.9	11.4	10.4	4.2
104.0	98.0	1.2	9.8	6.2	2.7
89.9	96.8	1.5	8.5	3.5	1.4
77.5	95.3	1.9	7.3	2.1	1.1
66.9	93.4	2.4	6.3	1.0	0.7
57.7	91.0	3.1	5.4	0.2	0.2
49.8	87.9	4.0	4.7	0.0	0.0
42.9	83.9	5.0	4.1	0.0	0.0
37.1	78.9	6.6	3.5	0.0	0.0
32.0	72.2	9.3	3.0	0.0	0.0
27.6	62.9	12.2	2.6	0.0	0.0
23.8	50.7	12.1	2.2	0.0	0.0
20.5	38.6	9.7	1.9	0.0	0.0

$D(v,0.5) = 23.6 \mu\text{m}$
 $D(v,0.9) = 54.9 \mu\text{m}$
 $D(v,0.1) = 11.3 \mu\text{m}$
 $D(4,3) = 28.1 \mu\text{m}$
 $D(3,2) = 21.0 \mu\text{m}$
 Span = 1.9

B-6815

FIGURE 3-3. - Overview of "Gravimelt" chemical cleaning process.

bath (reaction times of up to 4 h), the coal sample was removed from the reactor, water washed, and finally acid washed to generate an ultraclean coal product. Ash levels in the final coal of 0.5 to 1% were typical of the samples considered for and eventually used in this project. Process parameters used in the production of the two samples studied in this

program are shown in Table 3-6. Ultimate and ash analyses for these samples are contrasted with the Phase I Kentucky #9 bituminous coal, considered a generic parent fuel for this process, in Table 3-7. Moisture and volatile matter values varied considerably among three analytical labs used by DOE/PETC to analyze these samples; proximate analyses are therefore not reported, although the observed range is shown. Values in the table are presented on a moisture-free basis. Kentucky #9 analytical data were taken from the PSIT Phase I Final Report (Boni et al., 1990). Note that ash levels for the actual parent Kentucky #9 and Pittsburgh #8 samples were 8.9 and 10.9% respectively, as determined by UNDEERC. Apart from the volatile matter and moisture ranges reported, Gravimelt analytical data reported here are from one laboratory - Coors Analytical Laboratories - as obtained by DOE/PETC. Additional ash chemical X-ray fluorescence (XRF) analysis performed by UNDEERC through a co-operative agreement with DOE/PETC was comparable to the Coors analysis for most elements; as shown in Table 3-8, sulfur and sodium were notable exceptions. Because of the volatility of these two species, it is difficult to identify a "correct" set of data. The Coors analytical data have been arbitrarily chosen as the "correct" data for consistency in the latter sections of this report.

As the data in Tables 3-7 and 3-8 indicate, little difference was observed between these two deeply cleaned Gravimelt samples. In both cases, silicon dominated the ash oxides, with aluminum, iron, and alkali all present in approximately equal quantities. Comparison of the Gravimelt 7A sample with the Kentucky #9 coal in Table 3-7 reveals fairly uniform removal of most inorganic species. The increased concentration of sulfur in the Gravimelt ash suggests that sulfur removal was slightly less efficient than the removal of other elements. The increased concentrations of alkali suggest either incomplete alkali removal, or partial alkali retention during the cleaning process. Total alkali concentrations in the *coal*, however, have decreased by a factor of 3-5 during the cleaning process for these particular samples. Relatively high titanium concentrations were also observed in the ash of both Gravimelt coals, suggesting that Ti minerals were not as readily removed as others. Titanium (rutile) is one of the few minerals often present (primarily) as small inclusions in bituminous coals (Allen and VanderSande, 1984; Palmer and Filby, 1984); it is conceivable that these were not extracted with high efficiency due to mass transfer limitations. Solubility is not the issue, as rutile is alkali-soluble.

Chemical fractionation was also used to assess the form of the major elements within the Gravimelt coals. In this procedure, successive extractions are performed with water, ammonium acetate, and hydrochloric acid to remove chlorides, salts of organic acids, and oxides and carbonates, respectively (Benson and Holm, 1985). Insoluble clays and pyrite typically constitute the remaining "non-extractables." Chemical fractionation results obtained

TABLE 3-6. - Gravimelt coal sample preparation conditions

Sample	Parent Coal	Caustic/Coal Ratio (wt/wt)	NaOH (%)/ KOH (%)	Kiln Temperature (°C)
7A	Kentucky #9	2.5/1	50/50	427
9C	Pittsburgh #8	2.5/1	100/0	438

TABLE 3-7. - Gravimelt sample 7A and 9C coal analysis (dry basis)

	Phase I Kentucky #9	Gravimelt 7A (Kentucky #9)	Gravimelt 9C (Pittsburgh #8)
Volatile matter (dry, wt%)	37.6	24-26	20.5
Moisture (wt%)	8.3	17-47	6-46
Ultimate (wt%) (dry)			
C	65.4	79.4	79.7
H	4.7	3.5	3.8
N	1.8	1.8	1.6
S	3.9	0.7	0.4
O (difference)	8.6	14.0	14.1
Ash	15.6	0.6	0.4
Ash composition (wt%)			
SiO ₂	44.6	30.3	29.9
Al ₂ O ₃	20.6	11.3	10.6
TiO ₂	1.1	8.0	10.9
Fe ₂ O ₃	22.4	6.5	12.6
CaO	3.1	3.9	2.9
MgO	1.1	1.6	2.9
Na ₂ O	0.9	5.4	5.1
K ₂ O	2.6	7.5	2.9
SO ₃	4.7	25.5*	23.4*
P ₂ O ₅	0.1	—	—
Chlorine (ppm of coal, wt)	700	107**	<43**
*By difference.			
**Galbraith Analytical Labs on as-received sample.			

at UNDEERC for the two Gravimelt coals are reported in Table 3-9. For both coals, calcium and potassium were highly water soluble, indicative of calcite and possibly chlorides. Silicon and aluminum were largely insoluble in all solvents, indicating the presence of residual quartz and/or clays in both coals. Sodium was water soluble as expected in coal 9C; the low solubility observed in coal 7A was surprising. As discussion in later sections of this report will indicate, the volatility of the sodium in Gravimelt 7A suggests that it was not in clay mineral form. The sodium chemical fractionation results have therefore been discounted for Gravimelt 7A. Low residual iron levels for both coals are indicative of a lack of pyrite in these samples.

TABLE 3-8. - Comparison of Gravimelt sample 7A and 9C coal ash analyses (wt%)

	Sample 7A		Sample 9C	
	Coors	UNDEERC	Coors	UNDEERC
SiO ₂	30.3	30.5	29.9	25.7
Al ₂ O ₃	11.3	12.5	10.6	9.4
TiO ₂	8.0	7.9	10.9	14.8
Fe ₂ O ₃	6.5	12.7	12.6	11.1
CaO	3.9	4.1	2.9	2.6
MgO	1.6	0.6	2.9	1.5
Na ₂ O	5.4	11.7	5.1	11.4
K ₂ O	7.5	6.6	2.9	4.3
SO ₃	25.5*	12.4	23.4*	16.3
P ₂ O ₅	—	0.7	—	2.8
*By difference				

TABLE 3-9. - Chemical fractionation of Gravimelt coals

Element	Sample 7A				Sample 9C			
	% Removed by:			% Remaining	% Removed by:			% Remaining
	H ₂ O	NH ₄ OAc	HCl		H ₂ O	NH ₄ OAc	HCl	
Na	6	2	1	91	100	0	0	0
K	80	6	1	13	100	0	0	0
Mg	47	5	10	38	0	0	0	100
Ca	75	15	10	0	78	0	22	0
Al	3	3	6	88	30	0	0	70
Si	1	2	2	95	27	0	0	73
Fe	3	1	74	22	10	0	90	0

The reader should note that in recent Gravimelt developmental work, the process has been modified from that used to produce these samples (Anastasi et al., 1992). For example, the target ash level has changed to approximately 1.5 to 2%, NaOH is the only caustic used, and all wastewater streams have been eliminated. The previously achieved low sulfur levels (as low as 0.3% in the coal) are maintained, however. The reader should bear in mind that these changes in the Gravimelt process do not affect the conclusions of our ash formation study. The study of ash formation in these coals was not meant as an analysis of the Gravimelt process, but rather as a study of ash formation processes in deeply cleaned, chemically beneficiated coals.

3.3.3 Loy Yang 1953 Australian Brown Coal

During Phase I of this program, a brown coal sample obtained from the Loy Yang coal field of the State Electricity Commission of Victoria, Australia, was studied. This low ash, high sodium and chlorine sample from test bore 2301 proved ideal for studying alkali vaporization, alkali vapor phase molecular species evolution, and alkali-silica interactions (Boni et al., 1990, Sections 5, 7, and 6, respectively). In the Phase I work, experimental results at the University of Arizona indicated that sodium vaporization was related to the sodium to silica or sodium to aluminosilicate ratio of the parent coal. While the U.S. coals in this program contained low-to-moderate sodium/silica, the Loy Yang 2301 provided an example of a very high sodium/silica coal. Coals with intermediate sodium/silica were lacking, however, in this data set. To fill this gap, and provide an example of a very low ash, low-rank coal for study, another Loy Yang test bore sample was added to the test matrix for this program. After consultation with the Herman Research Laboratories of the SECV, Loy Yang 1953 was selected.

Analyses of the Loy Yang 1953 coal and Loy Yang 2301 from Phase I are presented in Table 3-10. Compared to the U.S. coals of Phase I and Phase II of this program, the brown coals contain high levels of sodium, chlorine, and magnesium, and unusually low levels of silica and aluminosilicates. A more detailed description of the mineralogy of these coals is presented in Section 4 of this report.

3.3.4 Kentucky #9/Eagle Butte Blend

Title IV of the Clean Air Act Amendments of 1990 requires that U.S. utilities limit SO₂ emissions to 2.5 lb/MMBtu by 1995 (Phase I limitation) and 1.2 lb/MMBtu (Phase II limitation) by 2003 (not allowing for the complexities of emissions trading; Stensvaag, 1991). Much of the power generation capacity affected by this legislation is choosing coal switching or coal blending as a means of controlling sulfur emissions. This implies that utilities may soon begin burning low-rank fuels in units designed for bituminous coals. Because the mineralogy of low-rank fuels is different from that of bituminous coals, the chemical composition and perhaps the size of the ash particles may differ significantly from bituminous coal ashes. Blending the two fuels types will therefore produce ash of some intermediate size and composition. It is not clear, however, whether the resulting ash will be an arithmetic mean of the parent ashes (no interaction among the blend component coals), or

TABLE 3-10. - Loy Yang 1953 and 2301 coal analyses

	Loy Yang (1953)*	Loy Yang (2301)**
Proximate (wt%)		
Fixed carbon	30.4	41.6
Volatile matter	36.1	44.2
Ash	2.0	1.3
Moisture	31.5	12.9
Proximate (dry basis)		
Fixed carbon	44.4	47.8
Volatile matter	52.7	50.8
Ash	2.9	1.4
Ultimate (dry, wt%)		
C	64.2	67.3
H	4.6	4.8
N	0.9	0.5
S	0.4	0.3
O (difference)	27.0	25.7
Ash	2.9	1.4
Ash composition (wt%)		
SiO ₂	11.8	9.4
Al ₂ O ₃	5.2	4.7
TiO ₂	0.3	0.7
Fe ₂ O ₃	15.9	16.3
CaO	3.4	3.8
MgO	22.2	14.5
Na ₂ O	13.5	30.7
K ₂ O	0.7	0.7
SO ₃	26.5	19.3
P ₂ O ₅	0.5	—
Chlorine† (ppm)	3200	5000
*Analysis by UNDEERC. **Analysis by SECV, numbers CS/87/256 and CS/88/59. †Analysis by Galbraith Analytical Labs on as-received samples.

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

2 of 6

will represent complete mixing (i.e., complete interaction among the ashes from the parent coals). Deposition behavior associated with these two extremes may differ dramatically. By studying the fundamental ash formation pathways for coal blends, insight into these important and timely issues can be gained.

In Phase II of this program, therefore, a blend of Eagle Butte sub-bituminous coal from the Powder River Basin and Kentucky #9 bituminous coal from the Illinois Basin was added to the test matrix. These coals were selected because they had been studied individually in great detail in Phase I of this program. It is recognized that the 70/30 blend is not a "Phase II compliance coal" as the sulfur levels remain above the 1.2 lb/MMBtu limit. Because our interest is in studying the fundamentals of the ash formation process rather than sulfur emissions, this was not an issue of concern.

The University of North Dakota Energy and Environmental Research Center was therefore contracted to acquire, pulverize, characterize, and distribute a 70/30 by weight Eagle Butte/Kentucky #9 blend by DOE/PETC. Reserves from Phase I were considered inappropriate because of partial oxidation of the pyrite in the coals as determined by Mössbauer analysis at the University of Kentucky. Efforts were made to match the Phase I Kentucky #9 and Eagle Butte as closely as possible. As the analyses of the parent coals in Table 3-11 indicate, these efforts were successful. Analytical data for the blend, presented in Table 3-12, shows that blending was also successful as the blend analysis was close to that calculated from the parent coal analyses assuming an exact 70/30 blend. In all cases, Phase I data were taken from Section 3 of the Phase I Final Report (Boni et al., 1990). Phase II data were obtained by UNDEERC. The measured coal particle size distribution for the blend (Malvern analysis at UNDEERC) is given in Table 3-13.

3.4 Summary of Phase I and Phase II Coal Analytical Data

Table 3-14 contains a summary of the Phase I coal analytical data. Table 3-15 contains a summary of the Phase I ash analytical data. The data in both tables are taken directly from the Phase I Final Report (Boni et al., 1990). Note that samples of these coals have also been provided by Foster Wheeler during Phase I to Sandia National Laboratories, where they have been extensively characterized and tested. Analytical results obtained by Sandia were nearly identical to those presented here with the exception of ash fusion temperatures for the Eagle Butte coal. Complete analytical results were summarized in a recent Sandia Quarterly Progress Report (Hardesty et al., 1992).

Coal and ash data for the Phase II coals are summarized in Table 3-16.

3.5 Summary of Coal Mineralogical Analysis by CCSEM

The measurement of the size and composition of a statistically significant sample of coal minerals by computer controlled scanning electron microscopy (CCSEM) was discussed in detail in the Phase I Final Report (Boni et al., 1990). Additional discussion is provided in Section 4 of this report. CCSEM analyses of all Phase I and Phase II coals are therefore

TABLE 3-11. - Eagle Butte and Kentucky #9 parent coal analysis (dry basis)

	Phase I Eagle Butte	Phase II Eagle Butte	Phase I Kentucky #9	Phase II Kentucky #9
Proximate (dry, wt%)				
Fixed carbon	48.4	46.1	46.8	45.2
Volatile matter	45.1	48.1	37.6	39.9
Ash	6.4	5.8	15.6	14.8
Ultimate (dry, wt%)				
C	67.2	71.2	65.4	68.2
H	5.0	5.1	4.7	4.8
N	1.4	0.9	1.8	1.3
S	0.5	0.5	3.9	4.4
O (difference)	19.5	16.6	8.6	6.5
Ash	6.4	5.8	15.6	14.8
Ash composition (wt%)				
SiO ₂	28.4	23.8	44.6	41.5
Al ₂ O ₃	15.5	14.0	20.6	18.1
TiO ₂	0.9	1.3	1.1	0.6
Fe ₂ O ₃	6.1	5.9	22.4	22.3
CaO	26.4	25.7	3.1	7.0
MgO	6.2	9.0	1.1	1.4
Na ₂ O	2.0	1.2	0.9	0.7
K ₂ O	0.2	0.3	2.6	1.8
SO ₃	13.7	18.1	4.7	6.1
P ₂ O ₅	0.7	0.8	0.1	0.5

TABLE 3-12. - Eagle Butte/Kentucky #9 coal blend analysis; measured versus calculated

	Blend Measured	Blend Calculated
Proximate (wt%)		
Fixed carbon	36.3	36.2
Volatile matter	34.5	35.7
Ash	7.3	7.1
Moisture	21.8	21.1
Proximate (dry basis)		
Fixed carbon	46.5	45.8
Volatile matter	44.2	45.2
Ash	9.4	9.0
Ultimate (dry, wt%)		
C	68.8	70.6
H	5.0	5.0
N	1.0	1.0
S	1.9	1.7
O (difference)	13.9	13.7
Ash	9.4	9.0
Ash composition (wt%)		
SiO ₂	30.1	—
Al ₂ O ₃	15.1	—
TiO ₂	0.9	—
Fe ₂ O ₃	14.2	—
CaO	15.8	—
MgO	3.3	—
Na ₂ O	1.2	—
K ₂ O	1.2	—
SO ₃	17.7	—
P ₂ O ₅	0.6	—

TABLE 3-13. - Malvern measurement of blend coal PSD

Size Microns	Under	% in Band	Size Microns	Under	% in Band	
188.0	100.0	0.7	17.7	34.4	3.5	
162.0	99.3	2.1	15.3	30.9	3.0	
140.0	97.2	3.2	13.2	27.9	2.4	
121.0	94.0	4.4	11.4	25.5	2.9	
104.0	89.6	5.0	9.8	22.6	3.9	
89.9	84.6	5.8	8.5	18.6	3.7	
77.5	78.8	5.9	7.3	15.0	2.6	
66.9	72.9	5.5	6.3	12.4	1.6	
57.7	67.4	4.5	5.4	10.8	1.5	D(v,0.5) = 31.4 μ m
49.8	62.8	3.8	4.7	9.2	2.3	D(v,0.9) = 105.3 μ m
42.9	59.0	3.8	4.1	6.9	2.8	D(v,0.1) = 5.0 μ m
37.1	55.2	4.6	3.5	4.1	2.0	D(4,3) = 43.5 μ m
32.0	50.6	4.6	3.0	2.1	0.9	D(3,2) = 15.7 μ m
27.6	46.0	4.0	2.6	1.2	0.6	
23.8	42.1	3.8	2.2	0.5	0.2	
20.5	38.2	3.8	1.9	0.4		

summarized in Tables 3-17 and 3-18 of this section without comment on the analytical technique. Although the coals were not studied in this program. CCSEM data for the Gravimelt parents - Kentucky #9 and Pittsburgh #8 - have also been included in Table 3-18. In general, CCSEM revealed smaller mineral size distributions in the cleaned coals than in the Phase I coals, indicating preferential removal of the largest minerals during both of the beneficiation processes considered here.

TABLE 3-14. - Fuel analysis for eight Phase I coals

	Upper Freeport			Beulah			Eagle Butte			Kentucky #9			San Miguel Lignite			Kentucky #11			Loy Yang 2301			Illinois #6		
	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry	As	Rec'd	Dry
Air Dry Loss, %	0.37			20.0			7.69			2.14			9.88			3.39						12.08		
Proximate Analysis																								
Fixed carbon	52.27	52.54		30.91	44.27		36.22	48.43		42.86	46.75		13.18	16.68		41.90	43.65		41.6	47.8		42.15	48.3	
Vol. matter	23.99	24.11		29.28	41.92		33.76	45.13		34.49	37.62		25.59	32.38		33.79	35.21		44.2	50.8		35.52	41.43	
Ash	23.23	23.35		9.65	13.81		4.82	6.44		14.33	15.63		40.26	50.94		20.79	21.14		1.3	1.4		8.62	9.94	
Moisture	0.51	-		30.16	-		25.20	-		8.32	-		20.97	-		4.02	-		12.9	-		13.31	-	
Total	100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.0	100.0		100.00	100.00	
Ultimate Analysis																								
Carbon	64.57	64.90		41.30	59.13		50.26	67.20		59.98	65.42		23.10	29.23		58.06	60.49		58.6	67.3		59.87	69.05	
Hydrogen	4.07	4.09		2.92	4.18		3.77	5.04		4.27	4.66		2.67	3.38		4.41	4.60		4.2	4.8		4.55	5.25	
Oxygen	3.92	3.94		13.84	19.82		14.60	19.51		7.92	8.63		11.22	14.20		7.74	8.06		22.4	25.7		8.52	9.83	
Nitrogen	1.63	1.64		0.82	1.18		1.01	1.35		1.63	1.78		0.41	0.52		1.18	1.23		0.4	0.5		1.37	1.58	
Sulfur	2.07	2.08		1.31	1.88		0.34	0.46		3.55	3.88		1.37	1.73		4.30	4.48		0.3	0.3		3.76	4.34	
Ash	23.23	23.35		9.65	13.81		4.82	6.44		14.33	15.63		40.26	50.94		20.29	21.14		1.3	1.4		8.62	9.94	
Moisture	0.51	-		30.16	-		25.20	-		8.32	-		20.97	-		4.02	-		12.9	-		13.31	-	
Total	100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.00	100.00		100.0	100.0		100.00	100.00	
H.H.V., Btu/lb	11,395	11,453		6,942	9,940		8,733	11,675		10,793	11,773		4,033	5,103		10,237	10,665		9,780	11,245		10,693	12,335	
Sulfate S	0.00	0.00		0.00	0.00		0.00	0.00		0.00	0.00		0.00	0.00		0.00	0.00		-	-		0.00	0.00	
Pyrite S	1.41	1.42		1.07	1.10		0.06	0.07		1.62	1.77		0.28	0.35		2.89	3.01		0.04	0.05		1.11	1.28	
Organic S	0.66	0.66		1.24	1.78		0.28	0.39		1.94	2.11		1.09	1.38		1.41	1.47		0.23	0.26		2.55	3.06	
Acid soluble alkalis (ppm)																								
Na	320/400	7500/7250		7500/7250	820/820		820/820	820/820		550/500	550/500		8969/7209	8969/7209		353/413	353/413		2900/3400	2900/3400		2177/2339	2177/2339	
K	2300/2400	150/170		150/170	80/110		80/110	80/110		2500/2600	2500/2600		5630/5591	5630/5591		3623/3214	3623/3214		-/-	-/-		2381/2378	2381/2378	
Ca	3700/3700	14125/13875		14125/13875	7000/8250		7000/8250	7000/8250		2900/2950	2900/2950		7723/7673	7723/7673		4981/4821	4981/4821		300/400	300/400		5792/5829	5792/5829	
Mg	1200/1200	3375/3250		3375/3250	1860/1890		1860/1890	1860/1890		850/850	850/850		1076/1163	1076/1163		920/946	920/946		1100/1300	1100/1300		1769/1762	1769/1762	
Chlorine (ppm)	-	95°/-		95°/-	-		-	-		700°/-	700°/-		500°/-	500°/-		-	-		5100°/-	5100°/-		1200°/-	1200°/-	

Note: Results are all based on Drum #7 retained at FWDC, except Loy Yang 2301 (SECV analysis).

TABLE 3.15. - Ash chemistry for eight Phase I coals

	Upper Freeport	Beulah	Eagle Butte	Kentucky #9	San Miguel Lignite	Kentucky #11	Loy Yang 2301	Illinois #6
% Ash (dry)	23.35	13.81	6.44	15.63	50.44	21.14	1.4	9.94
% S (dry)	2.08	1.88	0.46	3.88	1.73	4.48	0.3	4.34
Chemistry								
SiO ₂	50.6	21.6	28.4	44.6	65.7	45.8	9.4	46.1
Al ₂ O ₃	24.6	14.5	15.5	20.6	20.5	19.0	4.7	18.0
TiO ₂	1.2	0.0	0.9	1.1	0.9	0.9	0.7	0.9
Fe ₂ O ₃	13.5	12.2	6.1	22.4	1.8	20.4	16.3	20.5
CaO	2.2	17.1	26.4	3.1	3.2	4.4	3.8	5.3
MgO	1.4	4.2	6.2	1.1	0.5	0.9	14.5	0.6
Na ₂ O	0.3	6.1	2.0	0.9	2.0	0.3	30.7	1.3
K ₂ O	3.1	0.3	0.2	2.6	2.0	2.5	0.7	2.1
SO ₃	2.4	21.1	13.7	4.7	2.5	5.2	19.3	4.4
P ₂ O ₅	0.1	-	0.7	0.1	<0.1	0.1	-	0.1
Ash fusion temperatures (ASTM)								
<u>Reducing</u>								
Initial deformation	2178	1947	1996	1961	2309	2293	N/D	1863
Softening temperature (sph.)	2255	2087	2108	2043	2438	2300	N/D	1900
Softening temperature (hem.)	2320	2093	2149	2071	2491	2332	N/D	1935
Fluid temperature	2369	2106	2163	2126	2611	2353	N/D	1967
<u>Oxidizing</u>								
Initial deformation	2410	2168	2251	2231	2361	2299	N/D	2261
Softening temperature (sph.)	2496	2208	2308	2405	2422	2334	N/D	2220
Softening temperature (hem.)	2518	2217	2358	2436	2484	2366	N/D	2330
Fluid temperature	2536	2219	2358	2457	2593	2379	N/D	2495
Note: Results are all based on Drum #7 retained at FWDC, except Loy Yang 2301 (SECV analysis)								

TABLE 3.16. - Summary of coal and ash analyses for Phase II coals

	Illinois #6		Illinois #6 SOAP		Gravimelt 7A (Ky9)		Gravimelt 9C (Pitt8)		Kentucky #9		Eagle Butte		EB/K9 70/30 Blend		Loy Yang 1953	
	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry	As Rec'd	Dry
Proximate Analysis																
Fixed carbon	45.8	51.5	42.6	55.5	-	74	-	78	42.3	45.2	33.5	46.1	36.3	46.5	30.4	44.4
Volatile matter	34.7	39.0	31.4	40.9	-	25	-	21	37.3	39.9	35.0	48.1	4.5	44.2	36.1	52.7
Ash	8.4	9.4	2.8	3.6	-	0.6	-	0.4	13.8	14.8	4.2	5.8	7.3	9.4	2.0	2.9
Moisture	11.1	-	23.2	-	*	-	*	-	6.5	-	27.3	-	21.8	-	31.5	-
Ultimate Analysis (Dry)																
C	68.3		75.3		79.4		79.7		68.2		71.2		68.8		64.2	
H	4.9		5.3		3.5		3.8		4.8		5.1		5.0		4.6	
O	12.9		11.4		14.0		14.1		6.5		16.6		13.9		27.0	
N	1.2		1.4		1.8		1.6		1.3		0.9		1.0		0.9	
S	3.3		2.9		0.7		0.4		4.4		0.5		1.9		0.4	
Cl, ppm (As rec'd)	-		-		107		<43		-		-		-		3200	
HHV, Btu/lb	10,800	12,150	10,260	13,360	-	13,200	-	14,000 ⁺	11,600	12,400	9,250	12,720	9,820	12,560	7,230	10,550
Ash Chemistry (Wt%)																
SiO ₂	50.6		39.0		30.3		29.9		41.5		23.8		30.1		11.8	
Al ₂ O ₃	21.6		18.6		11.3		10.6		18.1		14.0		15.1		5.2	
TiO ₂	0.9		2.7		8.0		10.9		0.6		1.3		0.9		0.3	
Fe ₂ O ₃	18.4		27.1		6.5		12.6		22.3		5.9		14.2		15.9	
CaO	2.1		3.6		3.9		2.9		7.0		25.7		15.8		3.4	
MgO	1.2		1.4		1.6		2.9		1.4		9.0		3.3		22.2	
Na ₂ O	0.5		1.4		5.4		5.1		0.7		1.2		1.2		13.5	
K ₂ O	2.1		2.4		7.5		2.9		1.8		0.3		1.2		0.7	
SO ₃	2.2		3.5		25.5		23.4		6.1		18.1		17.7		26.5	
P ₂ O ₅	0.0		0.2		-		-		0.5		0.8		0.6		0.5	

*See Table 3.7 for range.

+ Estimated

TABLE 3.17 - Summary of CCSEM data for Phase I coals

Coal	Upper Freepport	Beulah	Eagle Butte	Kentucky #9	San Miguel	Kentucky #11	Illinois #6	Loy Yang [*] 2301
% Ash (dry)	23.4	13.8	6.4	15.6	50.7	21.8	9.9	1.4
Minerals (wt % of the mineral matter)								
Quartz	10	12	40	12	12	19	20	M
Kaolinite	7	30	13	6	2	8	6	T
Illite	35	1	2	23	-	16	10	I
Montmorillonite	1	1	2	-	16	1	-	T
Misc. silicates	19	13	16	34	64	23	18	M
Misc. sulfate	-	-	-	-	-	-	-	-
Pyrite	18	26	4	16	2	24	28	I
Fe sulfate	-	2	-	-	-	-	2	I
Fe rich	1	-	4	-	-	-	1	M
Alumina	-	-	-	-	-	-	-	-
Calcite	2	1	3	3	-	4	7	-
Mineral Size (μm) (cumulative volume % undersize)								
<5	19	34	34	45	25	39	39	-
<10	34	42	55	62	42	57	54	-
<20	49	55	70	77	68	70	77	-
<40	64	70	86	88	90	85	92	-

*M = major, I = minor, T = trace.

Table 3-18. - Summary of CCSEM data for Phase II coals

Coal	Illinois #6	Illinois #6 SOAP	Kentucky #9 (Gravimelt 7A Parent)	Pittsburgh #8 (Gravimelt 9C Parent)	Gravimelt 7A (Kentucky #9)	Gravimelt 9C (Pittsburgh #8)	Kentucky #9	Eagle Butte	Eagle Butte/ Kentucky #9 Blend	Loy Yang 1953
CCSEM Lab	U. Kentucky	U. Kentucky	UNDEERC	UNDEERC	UNDEERC	UNDEERC	UNDEERC	UNDEERC	UNDEERC	U. Kentucky
% Ash (dry)	9.4	3.6	8.9	10.9	0.6	0.4	14.8	5.8	9.4	2.9
Minerals (wt% of the mineral matter)										
Quartz	19.8	10.9	15.7	10.8	20.3	20.1	9.1	31.2	11.0	43.3
Kaolinite	4.5	0.1	6.1	12.6	5.7	1.3	11.4	30.5	12.8	0.2
Illite	7.4	1.1	6.6	5.8	7.6	1.2	19.2	0.5	14.8	-
Montmorillonite	-	-	1.1	1.4	0.7	0.7	3.2	1.9	2.6	3.8
Misc. silicates	28.7	18.5	2.2	1.8	9.7	6.3	2.7	4.0	2.5	23.6
Misc. sulfates	10.7	14.3	-	-	-	-	-	-	-	0.2
Pyrite	13.8	5.9	62.4	54.7	7.0	11.5	36.8	11.3	38.9	0.1
Fe sulfate	1.8	2.4	-	1.5	3.2	0.1	0.1	-	0.7	-
Fe rich	0.9	4.5	-	0.6	2.7	2.7	0.2	2.8	0.3	10.8
Alumina	0.2	5.9	0.1	-	0.5	4.7	-	-	-	0.6
Calcite	0.1	1.7	1.5	2.4	1.6	0.6	7.5	0.4	7.6	0.1
Mineral Size (μm) (cumulative volume % undersize)										
<4.6	-	-	59	58	57	62	25	62	53	-
<5	58	75	-	-	-	-	-	-	-	75
<10	77	92	77	77	80	95	59	78	78	78
<20	93	100	-	-	-	-	-	-	-	87
<22	-	-	91	94	90	100	72	89	89	-
<40	98	100	-	-	-	-	-	-	-	89
<46	-	-	100	99	100	100	92	98	99	-

*From Zygarlicke et al., 1992 (data for this sample)

3.6 References

Allen, R.M., and VanderSande, J.B. (1984) Fuel 63:1, 24.

Anastasi, J., Barrish, E., Battaile, B., McClanathan, L., Meyers, R., and Thridandam, H. (1992), "Molten-Caustic-Leaching (Gravimelt) System Integration Project," in Proceedings of the Eight Annual Coal Preparation, Utilization, and Environmental Control Contractors Conference, p. 368, July.

Bechtel National, Inc. (1990), "Advanced Physical Coal Cleaning Spherical Agglomeration," Draft Final Report submitted to U.S. DOE/PETC under contract no. DE-AC22-87PC79867, August.

Benson, S.A., and Holm, P.L. (1985), Ind. Eng. Chem. Prod. Res. Dev. 24, 145.

Boni, A.A., Helble, J.J. Srinivasachar, S., Sarofim, A.F., Beér, J.M., Bryers, R.W., Flagan, R.C., Peterson, T.W., Wendt, J.O.L., Huffman, G.P. and Huggins, F.E. (1990), "Transformations of Inorganic Coal Constituents in Combustion Systems," Phase I Final Report under DOE contract no. DE-AC22-86PC90751. NTIS Documents Numbers DOE/PC/90751-T4-90014467 and -90014468.

Gala, H.B., Srivastava, R.D., Rhee, K.H., and Hucko, R.E. (1989), Coal Preparation 7, 1.

Hardesty, D.R., Hurt, R.H., and Baxter, L.L. (1992), Coal Combustion Science Quarterly Progress report for the period January - March 1992, Sandia Report SAND92-8210 submitted to DOE/PETC under contract number DE-ACO4-76DP00789.

Hargrove, M.J., Chow, O.K., and Nsakala, N. ya (1991), "Combustion Characterization of Beneficiated Coal-Based Fuels," Topical Report on Microbubble Flotation Products and Spherical Oil Agglomeration Products submitted to U.S. DOE/PETC under contract number DE-AC22-89PC88654, June.

Palmer, C.A., and Filby, R.H. (1984), Fuel 63:3, 318.

Stensvaag, J.-M. (1991), "Clean Air Act Amendments Law and Practice," Wiley Law Publications, J. Wiley and Sons, New York.

Zygarlicke, C.J., Katrinak, K.A., Erickson, T.A., Folkedahl, B.S., Galbreath, K.C., McCollor, D.P., and Ramanathan, M. (1992), "Combustion Inorganic Transformations," Annual Technical Progress Report for the period 7/1/91 - 6/30/92 submitted to DOE/PETC under Cooperative Agreement No. DE-FC21-86MC10637.

SECTION 4

TASK 3

CHARACTERIZATION BY ADVANCED ANALYTICAL TECHNIQUES (UKY)

4. CHARACTERIZATION BY ADVANCED ANALYTICAL TECHNIQUES (UKY)

4.1 Introduction

The objective of this task is to apply modern, state-of-the-art, materials characterization techniques to thoroughly characterize the mineral matter and organically associated ash forming constituents in a carefully chosen suite of coals, and to apply the same methods to determine the transformations and reactions that these species undergo during coal combustion. The long range goal is to obtain a better understanding of the basic mechanisms of ash formation and slagging and fouling reactions.

In this section U. Kentucky analyses of MIT, UA, and PSIT coal and ash samples are summarized. For a detailed description of experimental techniques, sample collection, and analytical data interpretation, refer to Sections 5 (MIT), 6 (UA), and 7 (PSIT) of this report.

The analytical techniques that have been applied in this task and the information they provide can be summarized as follows:

(1) **Computer-controlled scanning electron microscopy (CCSEM)** - For coal minerals, this method provides a determination of the approximate weight percentages of the minerals present, as well as a size distribution of each significant mineral phase identified. For ash samples, the particles are categorized in tabular form in terms of the (up to) three major elements identified in their energy dispersive x-ray (EDX) spectra, with the results presented as both volume and number percentages. Size distributions are determined for the major ash species, and software has been developed for graphical presentation of ash chemistry in binary, ternary, and volume percentage - binary/ternary diagrams.

Phase II of this program, CCSEM analysis of coal and ash samples, was performed at both the University of Kentucky and the University of North Dakota Energy and Environmental Research Center. The samples analyzed by CCSEM are listed below; corresponding datasets are presented in Appendices L and M.

Directory of CCSEM Analytical Data Presented in Appendix L

	Table	Analytical Laboratory
1.	Illinois #6 SOAP Coal (Table 4-7)	UKY
2.	Illinois #6 coal (Table 4-8)	UKY
3.	Gravimelt 9C coal	UNDEERC
4.	Gravimelt 7A coal	UNDEERC
5.	Eagle Butte/Kentucky #9/Blend coals	UNDEERC
6.	Loy Yang 1953 coal (Table 4-5)	UKY

7.	Loy Yang 1953 coal	UNDEERC
8.	Treated Loy Yang 1953 coal	UNDEERC
9.	Beulah coal (Table 4-6a)	UKY
10.	Beulah coal (Table 4-6b)	UKY
11.	Beulah coal (Table 4-6c)	UKY
12.	Beulah coal	UNDEERC
13.	Kentucky #9 (Grav. 7A Parent) coal	UNDEERC
14.	Pittsburgh #9 (Grav. 9C Parent) coal	UNDEERC

Directory of CCSEM Analytical Data
Presented in Appendix M

	Table	Analytical Laboratory
1.	SOAP ash, 1500°C, surface	UNDEERC
2.	SOAP ash, 1500°C, X-S	UNDEERC
3.	SOAP ash, 1250°C, surface	UNDEERC
4.	SOAP ash, 1250°C, X-S	UNDEERC
5.	Gravimelt 9C ash, surface	UNDEERC
6.	Gravimelt 9C ash, X-S	UNDEERC
7.	Gravimelt 7A ash, surface	UNDEERC
8.	Kentucky #9 ash, SR=2.6, surface	UNDEERC
9.	Kentucky #9 ash, SR=2.6, X-S	UNDEERC
10.	Kentucky #9 ash, SR=1.0, surface	UNDEERC
11.	Kentucky #9 ash, SR=0.9, surface	UNDEERC
12.	Eagle Butte ash, SR=3.4, surface	UNDEERC
13.	Eagle Butte ash, SR=3.4, X-S	UNDEERC
14.	Eagle Butte ash, SR=1.0, surface	UNDEERC
15.	Eagle Butte ash, SR=0.9, surface	UNDEERC
16.	Blend ash, surface	UNDEERC
17.	Blend ash, X-S	UNDEERC

18.	Loy Yang 1953 ash, SECV HD (Table 4-69)	UKY
19.	Loy Yang 1953 ash, SECV ESP (Table 4-70)	UKY
20.	Treated Loy Yang 1953 ash, SECV HD (Table 4-72)	UKY
21.	Treated Loy Yang 1953 ash, SECV ESP (Table 4-73)	UKY
22.	Beulah ash, SECV CC (Table 4-56)	UKY
23.	Beulah ash, SECV HD (Table 4-57)	UKY
24.	Beulah ash, SECV ESP (Table 4-58)	UKY

(2) **Mössbauer spectroscopy** - Mössbauer spectroscopy using the ^{57}Fe nucleus determines the iron-bearing phases that are present in both coals and ashes, and the percentages of the total iron contained in each phase identified.

(3) **X-ray absorption fine structure (XAFS) spectroscopy** - XAFS spectroscopy can in principle be applied to determine the structure, or forms of occurrence, of any element in coal or ash. In the current investigation, however, it has been used primarily to determine the forms of calcium and potassium in coals and ashes. Additional applications have included the investigation of other elements, such as sulfur and iron in selected samples, in situ high temperature XAFS studies of the reactions of calcium, potassium, and iron, and preliminary studies of trace elements in several samples.

In the remainder of this report, we will first present a summary of experimental techniques, followed by a summary of the results obtained for Phase I coals, a summary of results obtained for the new coals investigated during Phase II of this program, and a summary of the results obtained for all ashes studied. The latter subsection, which is the longest in Section 4, will include data obtained from the ashes produced at PSIT, the University of Arizona, and MIT from the original coal suite selected for this program, data from new ash samples produced from Loy Yang, Beulah, and other coals derived from tests at the State Electricity Commission of Victoria (SECV) in Australia and the University of Arizona, results obtained from ash generated in drop-tube furnace tests at PSIT using a potassium-ion-exchanged Beulah lignite prepared at the University of Kentucky, and several model ash samples prepared in the Combustion Laboratory at MIT. Finally, the results of new XAFS spectroscopy experiments on high temperature, in situ, ash reactions, and on trace elements in coal and ash will be briefly discussed.

4.2 Experimental Techniques and Procedures

CCSEM Method for Coal:

The CCSEM at the University of Kentucky (UK) consists of a Tracor Northern 5500 system interfaced to an ISI 100 scanning electron microscope. Improvements and other changes in the software for the analysis of coal minerals, ash particulates, and other materials

have been developed in the course of this program for specific application at UK. Furthermore, methods have also been developed for transferring the data from the TN5500 to either personal computers or a MicroVAX II computer for both less costly data storage and more extensive analysis.

The CCSEM method, which was originally developed (Lee et al., 1978; Huggins et al., 1980) about 10 years ago and has been refined and enhanced continuously since (Huggins, et al., 1982; Huffman and Huggins, 1984; Huffman et al., 1986; Huffman et al., 1980; Shah et al., 1992), measures the areas of cross-section and the energy-dispersive spectra of at least 1200 different mineral particles in a random, polished section of the coal embedded in epoxy and reduces the data to derive the overall mineralogy of the coal. In the SEM, the electron beam is under the control of the computer and stepped across the field-of-view in a relatively coarse grid (256 x 256) in order to locate mineral particles in the coal/epoxy matrix. The back-scattered electron intensity is used to discriminate between mineral particles and the background of coal maceral and epoxy mounting medium. Once a mineral particle is located, the grid spacing is greatly reduced (4096 x 4096) and the area of cross section of the particle is measured by extending eight diagonals through the center of the particle to the edge of the particle and summing the areas of the triangles so produced. After the area is measured in this manner, the electron beam is positioned at the center of the particle and an energy dispersive X-ray (EDX) spectrum is collected for about 4s.

The chemical information contained in this spectrum is then used as a fingerprint to identify the mineral. The raw data on each particle, which includes information about its size, chemistry, and location, is stored in the computer memory. After typically 1200 particles have been measured in this way, the information is then passed to a second computer, a MicroVAX II, for reduction and analysis. In the most recent version of the CCSEM analysis, there are 25 individual mineral categories and fifteen mixed categories into which the EDX spectrum might fall. By analyzing at least 1200 particles in the coal section in this manner, a reasonably quantitative description of the coal mineralogy can be obtained.

Additional information that can be routinely obtained in the Coal Minerals Analysis is a semi-quantitative description of the size distribution of individual mineral categories and the overall mineral matter. Normally, if the size distribution of a particular mineral is of overriding interest, the CCSEM technique will have to be repeated a number of times to ensure that a sufficient number of particles of that type have been measured to give a statistically meaningful size distribution. However, for pyrite, it is possible to modify the CCSEM procedure to perform this analysis more efficiently by altering the back-scattered intensity discriminant threshold to distinguish between pyrite and other major minerals rather than between all minerals and macerals.

Analysis of the following Phase II coal samples is reported in this section:

Loy Yang 1953 (SECV)	Table 4-5
Beulah (SECV)	Table 4-6
Illinois #6	Table 4-7
Illinois #6 SOAP	Table 4-8
Mössbauer of Phase II coals	Table 4-4

All other Phase II coal samples were analyzed by UNDEERC. Data are reported in Appendix L. Phase I coal data are summarized in Section 3 and in Tables 4-1 through 4-3.

CCSEM techniques for ash samples:

CCSEM techniques for ash and slag samples are similar to those for the coal, except that the particles are not embedded in epoxy but are mounted on Nucleopore ($0.2\ \mu\text{m}$) filters by a process of filtration in triply-distilled acetone. The amount of material filtered is adjusted to give an optimum density of particles on the filter paper, which is judged through an optical microscope. Hence, the area that is measured is that which the particle extends normal to the electron beam and not a cross-sectional area. The volume of the particle is then estimated from the area measured.

Similar data reduction techniques are used as in CMA, but the sorting program is more generic and is based on the intensity of the energy-dispersive X-rays from the three most abundant elements, rather than on specific phases. The program identifies particles in which a single element, two elements, or three elements are dominant and labels them accordingly. For example, calcium-containing aluminosilicate glasses could fall into one of the categories, Ca-Si-Al, Si-Ca-Al, Al-Si-Ca, etc. The most abundant element in the class is first, and so on. Classes containing the same three elements are grouped together in the tabular outputs.

A variety of graphical methods have been developed for presenting the chemical information in the CCSEM ash data more clearly. These include the use of binary, ternary, and volume percentage/number frequency - ternary diagrams. Any element or combination of elements can be chosen as the endpoints or vertices of these diagrams. The threshold for the sum of the three elements in a ternary is set by the user; normally 80% is the value chosen, and this value should be assumed for all ternary diagrams in this report unless mentioned otherwise. Fourth elements may be indicated by vertical bars whose height is proportional to the percentage of the fourth element. On the color screen, fourth, fifth, etc., elements that exceed a user selected percentage (normally 5 to 10%) can be highlighted in different colors. The diagrams may be rotated or canted for better perspective views, and size distributions of selected regions of a ternary diagram are easily plotted. More detailed discussions of our methods of graphical representation of CCSEM data have been given elsewhere (Shah et al., 1992).

In addition to CCSEM studies of minerals and ash particles, we also investigated a number of deposit samples collected on ceramic tubes during combustion tests at SECV. These samples were cross-sectioned, mounted in epoxy, and polished. SEM micrographs and corresponding eight element X-ray maps were obtained from numerous areas for a number of deposit samples derived from combustion of both Beulah lignite and Loy Yang coal.

Analysis of the following mineral and ash samples is reported in this section (ϕ I denotes Phase I experiments):

Nepheline sample (PSIT)	Table 4-10
Montmorillonite sample (PSIT)	Table 4-11
Beulah ash (UA) (ϕ I)	Tables 4-12 through 4-15
Beulah ash (PSIT) (ϕ I)	Tables 4-16 and 4-17
Beulah ash (UA/PSIT)	Tables 4-48 through 4-55
Beulah ash (PSIT/SECV)	Tables 4-56 through 4-58
Beulah, ion-exchanged, ash (PSIT/UKY)	Tables 4-74 through 4-77
Eagle Butte ash (UA) (ϕ I)	Tables 4-18 and 4-19
Eagle Butte ash (PSIT/MIT) (ϕ I)	Table 4-20
Kentucky #9 ash (PSIT) (ϕ I)	Tables 4-21 and 4-22
Kentucky #9 ash (PSIT/MIT) (ϕ I)	Table 4-23
Kentucky #9 ash (UA) (ϕ I)	Table 4-24
Kentucky #11 ash (PSIT) (ϕ I)	Table 4-25
Kentucky #11 ash (UA) (ϕ I)	Table 4-26
Upper Freeport ash (UA) (ϕ I)	Tables 4-27 and 4-28
Upper Freeport ash (PSIT/MIT) (ϕ I)	Table 4-29
Illinois #6 ash (PSIT) (ϕ I)	Table 4-30
Illinois #6 ash (PSIT/MIT) (ϕ I)	Table 4-31
Illinois #6 ash (UA) (ϕ I)	Table 4-32
Illinois #6 ash (UA)	Tables 4-35 through 4-44
Illinois #6 SOAP (PSIT/UA)	Tables 4-45 through 4-47
San Miguel ash (PSIT) (ϕ I)	Tables 4-33 and 4-34
Loy Yang 2301 ash (UA)	Tables 4-59 through 4-64
Loy Yang 1953 ash (UA)	Tables 4-65 through 4-67
Loy Yang 1953 ash (PSIT/SECV)	Tables 4-68 through 4-71
Treated Loy Yang 1953 ash (PSIT/SECV)	Tables 4-72 and 4-73

⁵⁷Fe Mössbauer spectroscopy:

The Mössbauer technique is a nuclear gamma ray technique based on the resonant absorption and emission of gamma rays. Since its discovery in 1958, the Mössbauer effect has been identified in about 40 elements, but due to a combination of factors, the single most useful element for Mössbauer spectroscopy is iron. Not only is this the best element from an experimental point of view, but it also the Mössbauer element with the most general

applicability in all disciplines of science. This is particularly true for coal and related materials, because it is the only Mössbauer element with significant abundance in coal, and a large number of coal-related Mössbauer publications have appeared.

In Coal Minerals Analysis (CMA), Mössbauer spectroscopy is used to measure the relative abundance of the major iron-bearing minerals in coal: pyrite, iron-bearing clays (illite, chlorite) and siderite, to identify any weathering or oxidation products of pyrite, and to recognize any unusual iron minerals, for example, magnetite, that can be captured during heavy-media cleaning. This information is then used in the CMA to resolve ambiguities in the CCSEM analysis. Furthermore, the Mössbauer technique will also provide a direct measure of the pyritic sulfur content of the coal (Huffman and Huggins, 1978) that is more precise than the traditional chemical determination.

Mössbauer spectroscopy procedures for ash and slag samples are similar to those for coal and the technique determines the major iron-bearing components in the ash, usually iron oxides and iron-bearing aluminosilicate glass (Huffman et al., 1981). Such information is particularly valuable because iron is the most important basic element in U.S. bituminous coals that may participate in reactions to produce molten aluminosilicate slag droplets in a coal flame. Additionally, iron oxide/iron sulfide particles derived from pyrite constitute a sticky or partially molten species that has a high probability of depositing on furnace walls and tubes.

All Mössbauer spectra obtained in this study were taken using conventional constant acceleration spectrometers (Huffman and Huggins, 1978) with radioactive sources consisting of 50 to 100 mCi of ^{57}Co in a Pd matrix. The specimens were normally -100 to -200 mesh powders mounted in thin plexiglass holders for transmission spectroscopy. For some samples, spectra were obtained at temperatures as low as 10 K using an Air Products Displex cryogenic system.

XAFS spectroscopy:

X-ray Absorption Fine Structure (XAFS) spectroscopy has been used to examine important basic elements, such as calcium, potassium, and iron in the combustion samples generated in this investigation (Huffman et al., 1989; Srinivasachar, et al., 1990). This technique is similar to Mössbauer spectroscopy in that a specific element is examined and information is obtained on the bonding and structure of that element in the material at dilute concentrations (less than 0.1 wt%). By comparison with standard materials, the phase in which the element is contained can often be identified. Unlike Mössbauer spectroscopy, however, virtually any element in the periodic table can be examined by "tuning" the energy of the monochromatic X-rays irradiating the sample to the energy at which the characteristic edge absorption of the element occurs. The XAFS technique is limited procedurally due to the requirement that access to a synchrotron source of high-intensity X-rays is necessary in order to get the best quality data for the low-level abundance that many critical elements exhibit in coal and coal-derived materials.

XAFS spectroscopy utilizes the fine structure associated with an x-ray absorption edge of an element to determine the atomic structure of that element. The XAFS spectrum can be divided into two regions, the x-ray absorption near edge structure or XANES, and the extended x-ray absorption fine structure or EXAFS. The XANES is the structure within approximately 20 to 50 eV of the absorption edge. For K-shell XAFS spectra, it consists of a series of peaks derived from s→p transitions and scattering resonances of the photoelectron excited by the x-ray absorption, superimposed on a smooth step function corresponding to excitation of the photoelectron to the continuum. As we have discussed in detail elsewhere (Huffman et al., 1991), the ionization state of the absorbing element can sometimes be determined with high accuracy by the position of the s→p transition, while the percentage of the element occupying a given valence state can be determined from the s→p peak area. Least squares analysis of XANES features can provide quantitative phase percentage analyses in some cases. Frequently, however, the characteristic XANES spectra are used primarily as a fingerprint for identifying the major phase of a particular element in a sample without a detailed analysis.

The EXAFS is the oscillatory structure that starts at about 50 eV and extends up to 500 to 1000 eV above the absorption edge. It arises from interference between the outgoing and backscattered photoelectron waves generated by the x-ray absorption events. By isolating this part of the spectrum, converting from energy to wave vector space, and Fourier transforming, a radial structure function (RSF) is produced which is representative of the local atomic environment of the absorbing element. Further analysis of the RSF by back transforming and least squares fitting can yield reasonably accurate values for interatomic distances and coordination numbers of the first several shells of atoms surrounding the absorbing atoms.

4.3 Coal Analysis

In this section, data for the major inorganic constituents in all of the coals studied in this investigation are summarized. It is appropriate to first review the mineralogical data for the original seven coals selected for this study. The Mössbauer data are summarized in Table 4-1, which lists the percentages of the total iron contained in the iron-bearing minerals identified and the percentage of pyritic sulfur as determined from the Mössbauer measurement (Huffman and Huggins, 1978). As noted in our earlier final report for Phase I of this project (Boni et al., 1990), pyrite is the dominant iron-bearing species for all coals except Eagle Butte, which contains very little iron of any kind. Only Upper Freeport coal contains a significant amount of iron in phases other than pyrite, namely, siderite and illite. The absolute amount of pyrite is much less in the low-rank coals than in the bituminous coals.

The mineralogy of the original seven coals, determined by CCSEM, is summarized in Table 4-2. As discussed in more detail earlier (Helble et al., 1991; Helble et al., 1992), illite is the dominant clay mineral in the bituminous coals and is particularly high (35 wt% of the mineral matter (MM)) in Upper Freeport coal. Kaolinite is moderate in the bituminous coals (6 to 8% MM), but is dominant in the Beulah lignite (30% MM) and relatively high (13% MM) in Eagle Butte coal, for which quartz is the major mineral phase (40% MM).

The San Miguel lignite has 64% of its MM classified as mixed silicates and 16% as montmorillonite by the CCSEM software. However, as discussed previously (Helble et al., 1992), it appears that these phases are actually zeolites, probably from the heulandite-stilbite group and the mordenite group. Compositional data for these original seven coals are summarized in Table 4-3. A considerably more detailed discussion of the CCSEM results for these seven coals, including size distributions, and size and specific gravity fractionation results, is available in the Phase I final report (Boni et al., 1990).

Four of the seven coals had a significant calcium content and XAFS spectroscopy was used to determine the structure of the calcium. For the three low rank coals (Beulah, Eagle Butte, and San Miguel), calcium bonded to carboxyl groups and dispersed throughout the coal macerals was dominant, as has been observed for most other low-rank coals (Huffman and Huggins, 1984). This result for the San Miguel coal indicates that the zeolite phase contains a minor part of the calcium in the coal. The XAFS data for the Illinois #6 coal indicates that most of the calcium is present as calcite, but that a minor fraction is also contained as carboxyl-bound calcium.

In addition to the original suite of seven coals, a number of additional coals were selected for Phase II combustion tests at Arizona, PSIT, and SECV. These coals include new samples of Beulah lignite, Kentucky #9, and Eagle Butte, an Illinois #6 parent coal and the same coal after cleaning by a spherical oil agglomeration process (SOAP), Kentucky #9 and Pittsburgh #8 coals cleaned by molten caustic leaching (Gravimelt process), and two Loy Yang coals from Victoria (Australia). The Illinois #6 SOAP-cleaned coal and the Loy Yang coals contained very little mineral matter, making accurate analyses difficult. The Mössbauer analyses for these coals are summarized in Table 4-4. The CCSEM results are given in Tables 4-5 to 4-8. The dominant minerals in the Loy Yang 1953 sample are seen to be quartz and an iron-rich mineral identified by the Mössbauer spectrum as FeOOH. The Beulah lignite sample is that tested at SECV after approximately 2 years of storage in crushed form. The mineralogy exhibits some substantial differences from the Beulah sample used for previous tests. Three separate CCSEM runs were made on this coal, as shown in Table 4-6. It is seen that the dominant mineral category is "Miscellaneous sulfide," a phase whose EDX spectrum indicates a composition of approximately 15% Fe, 35% Ca, and 40% S. This is believed to be a mixture of calcium and iron sulfate formed by weathering reactions from pyrite and carboxyl-bound calcium in the fresh coal. Several percent of gypsum, ferrous sulfate and a mixed carbonate, which may also represent a weathering product are also observed. With the formation of these weathering products, the mineral species that were dominant in the fresh coal, kaolinite, pyrite, and quartz, are all decreased by roughly a factor of two. A wt%-ternary composition diagram for this phase is shown in Figure 4-1. It is seen that calcium sulfate, presumably gypsum, is the major species formed by reaction of sulfate ions with carboxyl bound calcium. Some iron sulfate is formed and some calcium-iron sulfate mixtures. Pyrite, however, is still the dominant iron phase. CCSEM results for the Illinois parent and SOAP cleaned product coals are given in Tables 4-7 and 4-8. It is seen that the clay minerals, illite and kaolinite are preferentially removed, while quartz, pyrite and mixed silicates are decreased by about 50%. The categories increased by SOAP cleaning, on a percentage basis, are miscellaneous sulfide and

mixed carbonate, which probably represent very small pyrite and other minerals included in coal particles.

XAFS spectroscopy analysis was carried out for a number of elements in a Pittsburgh #8 coal and a Kentucky #9 coal cleaned by the TRW molten caustic leaching (GRAVIMELT) process. The most complete analysis was done for sulfur. A typical least squares fitted sulfur K-edge XANES spectrum is shown in Figure 4-2. Using the method described elsewhere for determining sulfur percentages from such analyses (Huffman et al., 1991), the results given in Table 4-9 were obtained. For comparison purposes, we have included the results for a fresh Pittsburgh #8 coal from the Argonne premium coal sample bank. It is seen that the sulfur in the Gravimelt cleaned coals is severely oxidized, with sulfatic sulfur being the dominant component, followed by elemental sulfur, which is presumably formed during oxidation reactions of pyrite. Qualitative XANES results were also obtained for a number of other elements in these coals and may be summarized as follows:

- Chlorine appeared to be present as a chlorinated organic compound.
- Iron was present as FeOOH.
- Potassium, present as illite in the fresh coals, was present in an unidentified form, possibly KOH.
- Calcium and titanium were detected, but the specific forms could not be identified.

4.4 CCSEM Analysis of Pure Mineral Compounds

CCSEM runs were also made on two samples prepared from crushed powders of nepheline and montmorillonite, provided to UKY by PSIT. Unfortunately, as is often the case with mineral samples, these samples turned out to be multi-phase specimens. The results for the nepheline sample are given in Table 4-10 and Figures 4-3 and 4-4. The dominant phase is a Na-aluminosilicate that contains 6-10% K, while the second most abundant phase is a K-aluminosilicate containing from 0-8% Na. The ternary plots and volume percentage-ternary plots look quite reasonable; a tight cluster of points is exhibited by the Na-Si-Al diagram, which is very similar to the composition range of the nepheline phase formed during the combustion of Beulah lignite (see discussion in Sections 6 and 7 of this report; also, Boni et al., 1990). The composition is not far from the idealized composition of NaAlSiO_4 .

The data for the montmorillonite sample appear in Table 4-11 and Figures 4-5 and 4-6. The compositions in the tables and diagrams are seen to be silicon rich, and indicate an approximate stoichiometry of $\text{CaAlSi}_4\text{O}_{10}(\text{OH})$ for the Ca-Si-Al rich particles, and $\text{KAlSi}_4\text{O}_{10}$ for the K-Si-Al rich particles.

4.5 Ash Analysis

The current section is a summary of all analytical data obtained to date on the major constituents of ash samples generated in this investigation. It includes CCSEM data on the composition, size distributions, and volume percentages of all ash phases, Mössbauer data on the distribution of iron in iron-bearing ash phases, and XAFS data on the distribution of potassium and calcium in ash phases containing those elements. The samples reported include the ashes generated from the original seven coal suite selected for the study, new ash samples generated from Beulah lignite and Loy Yang coal in combustion tests at the University of Arizona (UA) and at SECV, additional ash samples generated at the UA from other coals, deposit samples collected on ceramic tubes during the tests at SECV, and ash samples generated in tests at PSIT using a potassium cation-exchanged Beulah coal prepared at UK.

4.5.1 CCSEM Data for Ash Samples from the Phase I Coals

The CCSEM data for the original seven coal suite selected for this study has been discussed in some detail in a number of publications. The results for both the low-rank coal ashes and the bituminous coal ashes were summarized in two papers at the Engineering Foundation Conference at Palm Coast by Helble et al. (Helble et al., 1992a, Helble et al., 1992b). Additional papers by Shah et al. have discussed the development of graphical methods for CCSEM data (Shah et al., 1991) and the reactions of calcium and alkalis with aluminosilicates during combustion (Shah et al., 1991). Extensive use of this data has also been made by the groups at PSIT, MIT and UA in the development of models for the prediction of fly ash formation, size distribution, stickiness, etc. These results have been reported in various quarterly reports and in other sections of the current report. The purpose of the current section, therefore, is not to present interpretive discussions of the results for the ashes from these coals, but simply to collect all of the data together in one place for future reference. Additionally, new and simpler methods for the tabulation and plotting of ash data have been developed over the past 2 years and results using these improved methods have not previously been presented for many of these samples.

4.5.1.1 *Beulah Lignite*

Ash samples from Phase I combustion tests (run 22) at UA on Beulah lignite were collected using an Anderson cascade impactor. CCSEM results for samples from impactors 1, 3, 5, and 7, run 22 are summarized in Tables 4-12 through 4-15 and Figures 4-7 through 4-12. The nature of the aluminosilicates in these samples have been discussed in some detail previously (Helble, 1992a), both for these samples and for drop tube furnace samples produced at PSIT. Briefly summarizing, the impactor 1 sample, which has the largest particles of the four samples (see Tables 4-12 through 4-15), exhibits the widest range of compositions in the Ca-Si-Al diagram. The composition of the Ca-aluminosilicate slag phase becoming more compacted near the center of the diagram as the particle size decreases with increasing impactor number. Additionally, the abundance of Fe-Si-Al and K-Si-Al slag particles is significant for the impactor 1 and 3 samples, but very minor for the smaller sized

impactor 5 and 7 samples. The origin of the potassium suggests possible contamination from a prior experiment. The Beulah ash was found to contain only 0.3% K_2O , which is consistent with the CCSEM identification of 1% of the mineral matter as illite, normally rare in low-rank coals, and a small percentage of K in the mixed silicate mineral category. However, 14 and 7%, respectively, of the impactor 1 and 3 samples are K-Si-Al rich ash particles with compositions very similar to illite. The previous experiment (run 21) utilized Illinois #6, which contained 2.1% K_2O and 10% illite. In later runs (32-33) with Loy Yang, carryover of sodium from run to run was observed. It is conceivable that in this early run, potassium carryover from Illinois #6 occurred, contaminating the next run - the ash of the Beulah lignite. Note that precautions to avoid this were taken in runs after run 33; it is therefore only a factor in early UA experiments.

A second point that has not been adequately discussed is the abundance of a mixed Ca-Na-sulfate phase in the small particle, impactor 7 sample (see Table 4-15 and Figure 4-12). This suggests the reaction of a fine particle CaO fume, a volatile sodium form, and SO_2 to form the fine, mixed sulfate particles captured on impactor 7. Because of the relatively low eutectic melting point ($920^\circ C$) of the Ca-Na sulfate system (Levin et al., 1964), this reaction is of some interest for deposit formation.

Two samples of Beulah lignite ash (Phase I coal) prepared in the drop tube furnace (DTF) of PSIT at different oxygen levels were also examined by the CCSEM technique. The results are summarized in Tables 4-16 and 4-17 and Figures 4-13 and 4-14. Similar to the impactor samples, these two samples also exhibit a wide range of compositions in the Ca-Si-Al diagram. With the increase in the oxygen level during combustion, interaction between the aluminosilicates derived from clays and calcium, which is initially atomically dispersed through the macerals increases. The volume frequency diagram for Ca-Si-Al for the two samples show that the particles are uniformly distributed for the higher oxygen level sample, whereas for the lower oxygen level sample, the particles are clustered near the Ca apex. This is indicative of reduced reaction between carboxyl-bound calcium and aluminosilicate minerals with reduction in oxygen level (i.e., reduction in particle combustion temperature). The second major category is that of 1:1:1 compositional ratio of Na:Si:Al which, in the final report of Phase I, was identified as nepheline. The composition range for this phase is somewhat tighter for the higher oxygen level combustion test. The K-rich categories are absent from these two samples which is normal for the low rank coals/ashes. Unlike the impactor samples, Fe from pyrite does not interact with the aluminosilicates derived from clays to form Fe-aluminosilicate slag. Additionally, little or no calcium or Ca-Na sulfate is observed. A substantial amount of Ca-rich particles is found in both samples, presumably as CaO or $Ca(OH)_2$. There is little unreacted quartz.

4.5.1.2 *Eagle Butte*

The results for impactor #1 and impactor #5 samples from the UA combustor (run 23) are presented in Tables 4-18 and 4-19 and Figures 4-15 through 4-17. As in the case of the Beulah lignite samples, the Ca-Si-Al composition range is more condensed in the smaller particle impactor #5 sample than in the impactor #1 sample. In both samples, however, the Ca-Si-Al composition range is broader than in the Beulah lignite ash. This probably occurs because of the presence of a large amount of quartz in Eagle Butte coal, which reacts with Ca directly to form calcium silicates, while kaolinite reacts to form calcium aluminosilicates. Again, there is a surprisingly large concentration (8%) of K-Si-Al enriched particles in the impactor #1 sample. As for the Beulah ash, the composition is similar to that of illite; however, only 2% of the coal MM was identified as illite. Contamination from prior runs (e.g., run 21) is therefore possible. The Fe-aluminosilicate (Figures 4-15 and 4-16) in this ash is also likely derived primarily from illite, since the pyrite content of the coal is very low. Nepheline (Na-Si-Al, Tables 4-18 and 4-19) is also formed, but in much lower concentration, because of the lower sodium content of the Eagle Butte coal. The absence of any significant Ca-Na-S phase is not surprising, in view of the very low sulfur content (0.27%) of this coal. A significant Ca-Mg-S phase is observed in the Im 5 sample, which is probably a Ca-Mg sulfate. The Ca-S-Al and Ca-S-Si phases, however, are probably unburnt char.

In the PSIT DTF ash produced from Eagle Butte, Ca-Si-Al slag is again the dominant phase (Table 4-20). Significant amounts of unreacted quartz and aluminosilicate are also observed. A Ca Mg Al phase, which also contains some Fe and Si, and a Ca Fe Al phase, which contains some Mg and Si, are fairly abundant in the PSIT ash from this coal. Volume percentage-ternary diagrams for the PSIT Eagle Butte ash are shown in Figure 4-18.

4.5.1.3 *Kentucky #9*

Two samples of Kentucky #9 ash prepared by PSIT at different oxygen levels and temperatures, and the impactor 1 sample from UA combustion run 24 were examined by CCSEM. The results are summarized in Tables 4-21 through 4-24 and Figures 4-19 through 4-22. Potassium aluminosilicate glass derived from illite is the dominant phase for all three samples (28-33%), followed by Fe-aluminosilicate slag derived from both illite and the reaction of illite and kaolinite with pyrite. The change in oxygen level and the change in temperature appear to have had very little effect on the composition of the ash phases formed. Calcium containing phases are notably enhanced for the UA impactor 1 specimen relative to the two PSIT samples. The UA sample exhibits 5 volume% Ca-rich phase, presumably CaO, 3% CaSO₄, and 10% Ca-aluminosilicate slag, compared with only a relatively minor amount of Ca-aluminosilicate phase for the PSIT samples. Carryover of small amounts of calcium from the previous experiment (Eagle Butte, run 23) may explain this finding. As seen from Figures 4-19 through 4-22, the amount of reaction between calcium and the aluminosilicates derived from clays is significantly less than observed for Beulah and Eagle Butte ash samples, reflecting the fact that the calcium is atomically dispersed through the low-rank coal macerals and is present as discrete calcite particles in the

Kentucky #9 coal. In all three samples there are significant amounts of unreacted quartz (11-13%) and unreacted kaolinite (6 to 16%), and a minor (1 to 3%), but interesting, Si-Al-Ti phase.

4.5.1.4 *Kentucky #11*

The results for the impactor 1 specimen derived from UA combustion run 27 and for the DTF sample prepared by PSIT are summarized in Tables 4-25 and 4-26 and Figures 4-23 through 4-25. They are very similar to the results obtained for the impactor 1 sample of Kentucky #9 coal. K-aluminosilicate glass and Fe-aluminosilicate slag are the two dominant phases in both the Kentucky #11 ash samples. Also, the calcium containing phases are enhanced for the UA impactor samples relative to the PSIT DTF sample. This includes the unreacted calcium derived from discrete calcite particles present in the coal which is higher in the UA sample than in the PSIT sample, and CaSO_4 which is present in a small amount in the UA sample and is absent in the PSIT sample. 2% by volume of Na-Si-Al particles are observed in the PSIT sample which was also observed in the PSIT sample of Kentucky #9. The minor Si-Al-Ti phase is again observed in both samples.

4.5.1.5 *Upper Freeport*

The results for UA run 32 for the impactor 1 and 3 samples of Upper Freeport ash and for a DTF run conducted by PSIT at MIT are given in Tables 4-27 through 4-29 and Figure 4-26. K-aluminosilicate slag and Fe-aluminosilicate slag are again the dominant phases, reflecting the large amounts of illite and pyrite in the coal mineral matter. Significant amounts of unreacted quartz and kaolinite, and a minor Si-Al-Ti phase are also observed. CaO and Ca-aluminosilicate phases observed in the UA impactor 1 and PSIT (overall) samples are replaced by a CaSO_4 phase in the smaller ash particles collected at UA (impactor 3 sample).

4.5.1.6 *Illinois #6*

The results for Illinois #6 ash samples prepared by PSIT in a DTF with 7% O_2 at two temperatures and by UA in test run 21 are given in Tables 4-30 through 4-32 and Figures 4-27 through 4-30. For all three samples there is a substantial amount of unreacted quartz and aluminosilicate derived from kaolinite. The reaction of calcium with aluminosilicates is somewhat greater than for the other bituminous coals, reflecting both the larger amount of calcium present for Illinois #6 and the fact that some of the calcium is dispersed as in the low-rank coals, as indicated by the XAFS data. In all of the samples, the dominant phase is K-Si-Al derived from illite, while the second most abundant phase is Fe-Si-Al derived from illite and from the reaction of pyrite with clay derivatives.

4.5.1.7 *San Miguel Lignite*

The results for the two San Miguel lignite ash samples prepared in the DTF at PSIT using different oxygen levels are given in the Tables 4-33 and 4-34 and Figures 4-31

and 4-32. There is a substantial amount of unreacted quartz, about 11% by volume, in both the samples and even greater amounts of unreacted aluminosilicates, 24% in the lower oxygen level sample and 33% in the higher oxygen level sample. Calcium and potassium aluminosilicates with a high Si/Al ratio derived from the zeolite in the coal are the major phases in ash. An aluminosilicate phase containing only a few percent of Ca and K, with approximately a 3/1 Si/Al ratio, is also very abundant. Also, there is an enhancement of Ca-aluminosilicates in the higher oxygen level sample as seen in the Figure 4-32. Minor amounts of a Na-Si-Al phase are observed in the higher oxygen level sample.

4.5.2 CCSEM Results for Ash Samples from Illinois #6 Parent and SOAP-Cleaned Coals

Four combustion tests were run on an Illinois #6 parent coal and one test was conducted on the SOAP-cleaned product from that coal at UA. The CCSEM results for the ash collected in these experiments are summarized below.

Illinois #6 parent, runs 47B, 47D, 47F, and 47H

The results are presented in Table 4-35 through 4-44 and Figures 4-33 through 4-39. For simplicity, only the results for samples from run 47B are shown graphically. Conditions for the runs 47B and 47D were apparently identical (1.4 kg/hr, 1304 C), but the samples for run 47B were collected at port 11 and those for run 47D at port 5. Similarly, the same combustion conditions (2.4 kg/hr, 1368 C) were used for runs 47F and 47H, but 47F samples were collected at port 11 and 47H samples at port 5. As summarized in the tables, the dominant phases for most of the samples are Fe-aluminosilicate derived from pyrite reactions with clay minerals and quartz, K-aluminosilicate derived from illite, and Ca-aluminosilicate derived from reaction between calcium present as calcite or other forms with clay minerals and quartz. In many of the samples, a significant amount of unreacted quartz, aluminosilicates, and iron oxide is observed. This is more prevalent in the impactor 1 samples. Calcium sulfate is also present as a minor phase in most samples. A Na-Si-Al aluminosilicate phase is present at the 1-2% level in many samples.

For most of the samples, there is a noticeable unburnt char component, which shows up in the tables as a high sulfur phase, e.g., S, S-Fe-Al, S-Si-Al, S-Si-Ca, and permutations of these combinations. In two samples, unburnt char is the dominant species. Ternary representations of the compositions of such particles are shown in Figure 4-39.

Fe-Si-Al aluminosilicates are the dominant ash species for most samples. From the ternary diagrams, it is seen that there is usually a cluster of particles near the iron-rich corner of the diagram, a major concentration of particles with compositions near the illite region of the diagram, and a somewhat sparsely populated range of concentrations between. The K-Si-Al diagrams all have the densest concentration in the illite composition range, while the Ca-Si-Al ternaries exhibit a range of compositions from the Ca-rich corner to the clay region of the diagram.

Additional discussion of this experiment is presented in Subsection 6.5.4.1 of this report.

Illinois #6 SOAP-cleaned coal, run 51B

As summarized in Tables 4-45 through 4-47, the K-Si-Al phase, the Ca-Si-Al phase, and the Si-Al rich particles have been virtually eliminated from the SOAP-cleaned Illinois #6 ash. The only substantial inorganic phase is Fe-Si-Al aluminosilicate. As seen from the ternary diagrams for this sample (Figures 4-40 through 4-43), there is a fairly uniform band of particle compositions from the Fe corner extending approximately 80% of the way across the diagram towards the Al-Si border; the Si/Al ratio for these aluminosilicates is about 3/2. These results suggest that the illite and kaolinite have been largely eliminated by the SOAP process, in accord with the CCSEM data for the coal (Table 4-8). The Fe-Si-Al phase is derived from the reaction of very fine pyrite and very fine mixed silicates that are left in the coal after the SOAP cleaning process. The percentage of unburnt char in the ash is significant and is present as Ca-S-Si, S-Fe-Si, and S-Al-Si in the tables. The inorganic composition of these char particles is illustrated in two of the ternary diagrams in Figure 4-40.

Additional discussion of this experiment is presented in Subsection 6.5.5.1 of this report.

4.5.3 CCSEM Results for Ash Samples from Beulah Lignite Coal

Three combustion tests were carried out on Beulah lignite coal at UA and three samples were collected from different locations in the combustor at the SECV. Note that while MIT, UA, and PSIT shared identical coal samples, the sample examined by SECV differed. Beulah lignite was shipped to SECV in crushed form and was not pulverized until the time of the test runs (approximately 2 years after shipment of the coal). Although the parent Beulah was identical to that used for the U.S. samples, the time delay (weathering) and use of a different pulverizer (SECV versus Foster-Wheeler) were expected to affect the coal mineralogy. The results for these samples from different combustors are summarized below.

Beulah lignite, runs 48B, 48D and 48F

The results from the three UA runs (see also Subsection 6.5.4.2) are given in Tables 4-48 through 4-55 and Figures 4-44 through 4-48. The combustion conditions were identical for the runs 48B and 48D (1.6 kg/hr, 1160°C) except for the port from which the ash samples were collected. For run 48B the sample was collected from port 11, whereas for run 48D the sample was collected from port 5. Higher feed rate and temperature (2.9 kg/hr, 1245°C) were used for run 48F. As observed in the previously analyzed Beulah ash samples, calcium containing phases are most dominant. Ca-Si-Al is the major calcium phase which occurs in all the samples in varying volumetric percentages. The percentage is high in the larger ash particles from the upper impactor plates (impactor 1 and cup) and varies

significantly in the lower impactor plates where the particles get smaller. The range of composition is similar to the previously analyzed PSIT Beulah samples. In addition to the glass phase, calcium is found to be present as isolated CaO and isolated CaSO₄, both in small but significant amounts. In all of the samples, the Ca-S phase is associated with Na with substantial mixing forming a Ca-S-Na phase. This appears to be a solid solution between CaSO₄ and Na₂SO₄. The Ca-S-Na phase is more dominant in the smaller ash particles. Some Ca-rich particles, presumably CaO, are found to coexist with other oxides to form minor phases like Ca-Si-Na (3-5% by volume) and Ca-Si-Mg (3%).

The nepheline phase is present in all the ashes irrespective of the positions of the impactor plates. The volume percentage varied from 1% to 15%. Na₂SO₄ and Na₂O are also present in a very small amount in some ash samples. Unreacted quartz and iron oxide are the significant single element categories in the larger particles. Small amounts of illite and pyrite in the coal react with the clays to form K-aluminosilicate glass and Fe-aluminosilicate slag.

The composition tables indicate that sulfur is present in significant amounts in almost all of the major phase categories. This suggests that the coals have not undergone complete combustion. Chemical analysis show the carbon content in one of the ash samples to be as high as 25% by weight, which confirms our conclusion. The unburnt char appears as phases such as Ca-Si-S in the CCSEM tables. This is observed in all the UA Beulah samples.

Beulah lignite, SECV run

Three Beulah ash samples from combustion tests at SECV were analyzed and the results are presented in Tables 4-56 through 4-58 and Figures 4-49 through 4-52. Two of these samples were collected from the ash probes placed in different sections of the combustion system, one in the combustion chamber and the other in the horizontal duct. The third sample was collected from the precipitator (see Figure 7-24 of Quarterly Report 19; Helble et al., 1991).

The SECV samples also contain significant amounts of Na-Si-Al phase or the nepheline phase. The composition range for Na-Si-Al phase is much wider in the two ash probe samples than in the precipitator ash sample, where it is reduced to a much narrower range. There is also some interaction between volatile sodium and quartz in all three samples. The concentration of Na-Al-Si phases observed here is higher than that seen in UA and PSIT experiments; perhaps residual Na from prior Loy Yang runs contributed. Interaction of pyrite and kaolinite is minimal, but rather extensive interaction of calcium, derived from the coal macerals, with aluminosilicates is shown in Figures 4-49 through 4-51. The interaction is less in the precipitator ash sample than in the ash probe samples.

As observed in the UA ash samples discussed earlier, carboxyl-bound calcium from the coal forms a Ca-S phase (CaSO₄), and frequently such phases are associated with iron-rich, magnesium-rich and sodium-rich phases. While there appears to be little compound formation between the CaSO₄ and iron-rich, magnesium-rich and silicon-rich oxide particles,

substantial mixing is observed for Ca-Na-S phase (Figure 4-51). As noted earlier, this could be a solid solution between Na_2SO_4 and CaSO_4 .

4.5.4 CCSEM Results for Ash Samples from Loy Yang Coal

Three combustion tests were carried out on Loy Yang brown coal at UA, two on Loy Yang 2301 coal and one on Loy Yang 1953. Three tests were also made by PSIT at the SECV on Loy Yang 1953, out of which one test was on a treated Loy Yang 1953. The other two tests were made before and after the treated coal was combusted. The results for these samples from different combustors are summarized below.

Loy Yang 2301, runs 49B, and 49H

The results for the two UA runs are presented in Tables 4-59 through 4-64 and Figures 4-53 through 4-59. Combustion conditions for both the runs were different (2.4 kg/hr and 1275°C for run 49B, and 3.8 kg/hr and 1420°C for run 49H) but the port for collection of the samples was same (port 11). In all of these UA samples, sulfur is found to be present in all of the major as well as minor categories, as observed in some previously discussed ashes. This very strongly suggests that the coals did not go through complete combustion or burnout. This was again confirmed by the carbon content test which was carried out on one of the ash samples. Substantial unburnt carbon was present in the ash.

The sulfur reacts with calcium to form CaSO_4 , which is one of the major binary phases found in the upper impactor plates. This phase reduced substantially in the lower impactor plates where the ash particles are smaller. Also, CaO is abundant in the larger particles. The other major phase present is Ca-S-Mg, which is dominant in most of the samples. Little interaction is observed between magnesium and sulfur for the impactor+cup samples where the principal phase observed is a combination of MgO-CaSO_4 . The interaction between MgO and CaSO_4 increases for the smaller particle samples. For stage 2+3+4 impactor samples mixtures of CaSO_4 , CaO-MgSO_4 , CaO-CaSO_4 , and MgO-CaSO_4 are observed. The smallest particle samples show phases that are richer in sulfur. The other calcium sulfate-rich, CaO-CaSO_4 , phase observed is admixed with chlorine for the most part. Chlorine, which is present in the coal as chlorine in solution in adsorbed water, may be forming CaCl_2 which in turn may be interacting with CaSO_4 . In the smaller particles, the stable forms NaCl and MgSO_4 are formed, although some calcium interaction is observed. Substantial amounts of NaCl particles in the 2 to 10 microns size range are found in the lower impactor plates.

No aluminosilicate rich phases are observed in any of the samples due to the lack of aluminosilicate minerals in the coal. Iron, assumed to be in the oxyhydroxide form in the coal, predominantly interacts with magnesium and calcium sulfate. Chlorine also interacts substantially with the sulfates without forming a distinct chloride phase with either calcium or magnesium.

Additional details are presented in Subsection 6.5.4.3 of this report.

Loy Yang 1953, run 50D

The results are presented in Tables 4-65 through 4-67 and Figures 4-60 through 4-62. Loy Yang 1953 coal is similar to the Loy Yang 2301 in its sodium and ash content. However, Loy Yang 1953 contains a higher percentage of ash as quartz than Loy Yang 2301. The combustion conditions for run 50D were 2.4 kg/hr feed rate, and 1160°C temperature. Similar to the previous samples, excessive sulfur is found in these samples also, due to incomplete combustion. The volume percent of the sulfur particles decreases with increasing impactor number.

Similar to the Loy Yang 2301 ash samples, CaSO_4 is a dominant phase in the two upper impactor samples and NaCl is dominant for the lower impactor sample (smaller particles). Ca-Al-S and Si-Al-S are the two major categories in the upper impactor plates and probably represent unburnt char. For the smaller particle samples there is an increase in the interaction of iron with calcium sulfate and also in the formation of magnesium sulfate along with sodium sulfate. Some K-rich phases also start to appear which become very prominent in the smallest particle sample, where iron, calcium, and sodium react with sulfur and potassium. Both the NaCl and Na_2SO_4 phases are formed in the smallest particle sample, and the latter also seems to interact with iron. Formation of aluminosilicate-rich phases are scarce, although more interaction is observed in these samples than observed in Loy Yang 2301 samples.

Additional details are presented in Subsection 6.5.4.4 of this report.

Loy Yang 1953, SECV runs

These results are summarized in Tables 4-68 through 4-73 and Figures 4-63 through 4-67. Three combustion runs identified as tests were carried out on Loy Yang 1953 coal at SECV. For Test #3 Loy Yang coal, treated with an $\text{Mg}(\text{OH})_2/\text{MgCO}_3$ mixture and water soluble $\text{Al}_2(\text{SO}_4)_3$, was burnt, to assess the impact of the addition of aluminum on ash formation. Addition of aluminum in the coal is suppose to reduce the formation of sodium-rich phases causing a decrease in the deposition in the reactor. For test #1 and test #4 untreated coal was burnt. Test #1 was carried out prior to the combustion of treated coal and test #4 was after the combustion of treated coal. Two samples from each test, one from the ash probe and the other from the precipitator plate, were analyzed.

Additional experimental detail for these experiments is described in Section 7 of this report.

The treated Loy Yang samples unfortunately exhibited a major contamination from zinc, presumably contained in the additive. Further discussion of this sample is provided in Section 7.

Both the untreated ash probe and precipitator ash samples for test 1 and test 4 exhibited a dominant Ca-Mg-Al phase (Figures 4-63 and 4-64). This was not observed in the

UA samples for this coal. There is a small amount of alumina (2%) in the coal. Presumably, this calcium-magnesium aluminate could arise from reaction of atomically dispersed calcium and magnesium in the coal macerals with the alumina (see coal characterization in Section 3 of this report). Si-Mg-Al and Fe-Mg-Al phases containing Ca were also observed (Figure 4-65). In the precipitator ash, NaCl and NaSO₄ phases were observed (Figure 4-66), as well as mixtures of Cl and Na with the Ca-Mg-Al phase. Minor amounts of a Na-Si-Al phase were also observed (Figure 4-67).

4.5.5 CCSEM Results for Ash Samples from Ion-Exchanged Potassium-Loaded Beulah Lignite Coal

Most of the potassium in coal usually exists in the discrete clay mineral form, illite. Such potassium remains associated with the aluminosilicate framework of the illite clay structure throughout combustion and does not interact with any other mineral matter in the initial stages of combustion process. It was therefore decided to examine the behavior of potassium which is not contained in clay minerals but which exists in molecularly dispersed carboxyl form in order to compare its behavior with the observed behavior of sodium in Beulah lignite. To create such a species, carboxyl-bound calcium and sodium in the Beulah lignite was ion-exchanged with potassium acetate at the University of Kentucky. Both the original coal and the ion-exchanged coal were then combusted in the drop tube furnace (DTF) at PSIT at 1500°C in 7% oxygen. The ion-exchanged ash samples were collected at 1 and 3s of residence time in the DTF.

The CCSEM results for these ash samples are summarized in Tables 4-74 through 4-75 and Figures 4-68 through 4-73. The ash samples derived from Beulah lignite without potassium ion-exchange are quite similar to those obtained from this coal in previous PSIT tests. Ca-Si-Al slag is the dominant phase in both the 1 and 3s residence time (RT) samples, constituting 44% of the former and 50 % of the latter. A Na-Si-Al phase with a composition range close to that of nepheline (NaAlSi₃O₈) is the second most abundant phase (7% for 1s RT, and 16% for 3s RT). The composition ranges for both phases are somewhat tighter for the 3s RT sample in both cases. For the K-ion exchanged sample, the Ca-Si-Al slag phase is still significant, but is substantially reduced in percentage (19% for 1s RT, 29% for 3s RT) because much of the Ca has been replaced by K. The Na-Si-Al nepheline phase is replaced by a K-Si-Al aluminosilicate phase (14% for 1s RT, 23% for 3s RT). For the 1s RT ash, the composition of the K-Si-Al phase is close to that of kalsilite (KSiAlO₄), the compositional analogue of nepheline. For the 3s RT sample, however, the composition is distinctly shifted towards the potassium corner of the diagram.

A K-Ca-S phase, presumably a mixed K-Ca sulfate, is also very significant in both ion-exchanged ash samples, constituting 20% of the ash for the 1s RT sample, and 11% for the 3s RT sample. The ternary diagrams in Figures 4-72 and 4-73 indicate that a K₂SO₄ - CaSO₄ - CaO solid solution has formed rapidly in the 1s RT ash. In the 3s RT ash, the sulfate has been partially destroyed by formation of Ca and K aluminosilicates. As discussed later, the presence of K₂SO₄ is confirmed by XAFS spectroscopy.

4.5.6 Ceramic tube deposition samples from SECV runs

These samples were collected by PSIT/SECV in the nominal 35 kg/hr pilot scale furnace of the SECV. An uncooled ceramic tip was attached to the end of the cooled deposition probe for 30 min to collect a short term deposition sample, and was removed and replaced by another ceramic tip for the duration of the run (4 to 6 hours) to collect a long term deposition sample. A schematic of the SECV furnace, Figure 7-24 in Quarterly Report No. 19 gives a better idea of the sampling location. Details are provided elsewhere (Section 7; also Helble et al., 1991).

The SEM sample preparation technique for the ceramic tube samples was similar to that of the coals. Tubes were cross sectioned using a diamond cutting tool, embedded in epoxy, polished, and coated with a thin layer of carbon.

For all the deposit samples, the ceramic tube was composed primarily of aluminosilicates with uniform dispersion of potassium. Figure 4-74 is a typical Energy Dispersive X-ray (EDX) spectrum for a region of the ceramic tube away from the deposition surface.

The long-term deposit for Loy Yang untreated coal (test #1) is rich in iron and an iron-rich layer seems to coat the ceramic tube. Figures 4-75 and 4-76 are the SEM micrograph and x-ray maps of major elements, respectively, for a region showing the deposition buildup on the tube. There is significant mixing of iron, calcium and aluminosilicates. Some potassium from the ceramic tube seems to have diffused into the deposit and mixed with the aluminosilicates. X-ray maps in Figure 4-76 show this diffusion of potassium along with the uniform composition of the ceramic tube. The silicon rich regions seem to coexist with calcium rich regions, whereas the iron rich regions are more distinct and separate. This mode of selective mixing is also very clearly seen in Figures 4-77 and 4-78. This is another region of the deposit accumulated on the surface of the ceramic tube. Calcium rich and iron rich phases with diffused potassium seem to dominate. Figure 4-79 shows deposition near the ceramic tube at a higher magnification. This region is predominantly a Ca-Fe-K glass phase with recrystallized hematite particles dispersed throughout.

No significant deposits are found for the short term test #1 sample whereas there are appreciable deposits in the case of short term (test #4) of Loy Yang untreated coal. Figures 4-80 and 4-81 are the micrograph and x-ray maps of major elements for this sample. Unlike the long term deposits for test #1, the iron-rich layer which coats the surface of the ceramic tube is absent in the short term deposit for test #4 sample. Instead, iron-rich particles are scattered throughout the deposit and appear to have stuck together with quartz particles but without any mixing between the two phases except at the boundary of the deposits and the ceramic tube surface. At the boundaries between the iron and silicon rich regions, there appears to be melting of the Fe-Si mixture. Figures 4-82 and 4-83 are the micrograph and x-ray maps of one such deposited region on the tube surface. The x-ray

maps also indicate K-Ca-Si mixing. The fact that potassium is diffusing from the ceramic tube into the deposits is very clearly seen in Figure 4-83.

The long-term deposit for test #4 of Loy Yang untreated coal is similar to the short term deposits. The iron rich and silicon rich (quartz) particles are very distinct and appear stuck together without much mixing. Figures 4-84 and 4-85 are the micrograph and x-ray maps of the deposit and Figures 4-86 and 4-87 show a magnification of one such iron-rich/silicon-rich region. There is very little-to-no interaction between the two phases except at the boundary where melting of Fe-Si may have occurred. Figure 4-88 is an EDX spectrum for a region which appears to be a boundary formed by melting of the two phases and probably holds the iron rich and silicon rich phases together. Unlike the short term deposit, an initial deposit mixture of Ca, Fe, Si, K, S, Na and Cl is formed. The deposit on the surface of the tube is much more richer in calcium, sulfur and sodium than in others. Figure 4-89 shows such an initial deposition X-ray map. A mixture of CaSO_4 and NaCl with an admixture of Fe and K is a good possibility. It again confirms the diffusion of potassium from the ceramic tube.

There is a significant amount of Mg and Ca in the ash probe samples of both tests. However, we see little or no Mg in either deposit sample, and we see no Ca in the deposit for test #4, but lots of Ca in the deposit for test #1. Our SEM results for test #4, which show primarily quartz and iron, agree with the chemical analysis of the deposit samples given in Table 7-24 and with the XRD analysis given in Table 7-23, Quarterly Report #19 (Helble et al., 1991).

As compared to Loy Yang deposit samples, the tests for Beulah lignite produced thicker deposits. For the short term sample, the deposit is inconsistent in the formation of an initial iron rich layer. Figures 4-90 and 4-91 are the micrograph and x-ray maps of the major elements for the short term deposit sample. Iron rich particles seem to agglomerate to form clusters near the tube surface without forming a uniform layer. Figure 4-91 shows sulfur in and around the iron rich particles. Along with the iron rich phases, the short term deposit is also rich in calcium. The potassium in the deposit presumably diffuses from the ceramic tube as observed for the Loy Yang deposit samples. Figures 4-92 and 4-93 are the micrograph and x-ray maps respectively for another region of this deposit. In this region the initial deposition layers seem to be rich in iron and calcium, iron uniformly coating the tube surface. Diffusion of potassium from the ceramic material is very prominent in the x-ray maps, as shown in Figure 4-93. The deposit in this region therefore consists of an iron-rich layer that appears to wet the tube surface, covered by a Ca-Na-K-silicate. It is noted that the Ca and alkalis are concentrated in different regions of the silicate phase. Sodium also contributes in the deposit formation. Potassium seems to form a mixture with quartz and sodium, and calcium rich phase seems to encapsulate the K-Si-Na rich phase.

The long-term deposit sample for the Beulah lignite coal is found to have the thickest deposit layer. The initial iron rich layer is very prominent in this sample also. Figure 4-94 shows this distinct iron rich layer as a thin, bright region on the tube surface. This iron rich layer is spread uniformly over the ceramic tube (Figure 4-95). There appears to be wetting

of the tube surface taking place by the iron rich phase. Figures 4-96 and 4-97 show one such region where this phenomena is prominent due to the rounded corners of the deposit. The deposit is a mixture of Fe, Ca, K and aluminosilicates. On the outer border of this deposit there is a Ca sulfate formation. Sodium is also mixed with both the aluminosilicate and sulfate, as is potassium, which is assumed to diffuse from the ceramic tube.

A region of the deposit away from the tube surface is shown in Figures 4-98 and 4-99. Ca, Fe, K and slight S enrichments occur in this region, indicating a mixed oxide-sulfate formation. For the most part, however, Ca-Fe-K-aluminosilicates are the dominant phases observed in this zone.

The outermost deposit is predominantly recrystallized phases. Figure 4-100 is a micrograph of one such deposit and Figure 4-101 show the EDX spectra of the marked regions. The basic matrix seems to be larnite (Ca_2SiO_4) with scattered Fe rich particles and recrystallized Ca-glass phase which are significantly Na-enriched and/or Fe-enriched. Similar observations are made for two other outer deposit regions and are shown in Figures 4-102 through 4-105. Ca-K-Fe aluminosilicates are the dominant phases.

4.5.7 Mössbauer Spectroscopy Results for Selected Ash Samples

Mössbauer spectra were obtained on four samples from the University of Arizona combustion experiments to investigate the conversion of pyrite to iron oxides and the concomitant incorporation of iron into aluminosilicate glass as a function of temperature and the oxygen conditions of the burn. These samples are the "cup + Im1" samples that represent all of the material reaching the impactor, without regard to size. Generally, the material on individual impactor filters, except for the first and coarsest filter (Im1), is insufficient to be useful for a Mössbauer experiment, especially if it is also to be used for XAFS and CCSEM investigations.

The four samples are as follows:

<u>U.K. I.D.</u>	<u>U. Az. I.D.</u>	<u>Sample Description</u>
650	56-6-CUP-A'	Ky #11 coal, Port 11 material, 1.4 kg/hr, 1240°C
653	56-6-CUP-D'	Ky #11 coal, Port 11 material, 2.4 kg/hr, 1430°C
656	57-6-CUP-A'	Ky #11 coal, Port 11 material, 1.8 kg/hr, 1120°C (sub)
659	58-6-CUP-C'	Ky #11 coal, Port 11 material, 1.8 kg/hr, 1440°C (sup)

sub - substoichiometric; sup - superstoichiometric.

The Mössbauer spectra of all samples appear to be a mixture of magnetic iron oxides (hematite and magnetite) and iron in non-magnetic phases, principally aluminosilicate glass.

Both Fe^{2+} and Fe^{3+} appear to be present in the non-magnetic phases, but there is significant variation among the four samples in the iron absorptions that make up this component. The results of the computer fitting of the spectra are shown in Table 4-78. The Mössbauer parameters listed in Table 4-78 for iron in aluminosilicate glass for the two highest-temperature runs are quite consistent with values expected for both Fe^{3+} and Fe^{2+} absorptions in glass. However, for the two lowest-temperature runs, the Mössbauer parameters for these absorptions are less consistent with iron in glass. For the substoichiometric run (57-6-CUP-A'), the parameters for one non-magnetic absorption are consistent with Fe^{2+} in glass, whereas the parameters for the other non-magnetic absorption appear to be very similar to those for pyrite (FeS_2 ; IS = 0.31, and QS = 0.62). Hence, in this sample, some residual pyrite may have survived the journey through the furnace without alteration. It should be noted that the Mössbauer spectrum of this sample also indicates the presence of a minor amount of iron sulfide (pyrrhotite, Fe_{1-x}S). Due to the low oxygen fugacity of the substoichiometric run, predominantly ferrous glass is formed. For the next lowest-temperature run (56-6-CUP-A'), the Mössbauer parameters for one absorption are consistent with Fe^{3+} in aluminosilicate glass and/or with superparamagnetic ferric oxides, whereas the other non-magnetic doublet may arise from superparamagnetic magnetite. Spectra at cryogenic temperatures would help to resolve some of these ambiguities and will be carried out in the future. These observations appear to imply that at relatively low temperatures, in the one case, ferric oxide is not easily incorporated into the aluminosilicate glass, while, in the other case (the substoichiometric run, 57-6-A'), ferrous iron is readily incorporated into glass, despite the significantly lower temperature of the run.

With the differences in temperature and oxygen conditions, there is consistent variation in the hematite/magnetite ratio for the four samples. Generally, lower temperatures will favor the formation of hematite relative to magnetite; however, in these four samples, the substoichiometric run of lowest temperature has the lowest ratio of hematite relative to magnetite. This occurs, presumably, due to the consumption of all free oxygen in this run, which inhibits hematite formation. The next lowest-temperature run is the one with the highest ratio of hematite to magnetite. For the two highest-temperature runs, the superstoichiometric run has a significantly higher hematite/magnetite ratio, despite the similarity of the temperature of these runs. This observation can be attributed to the excess oxygen in the superstoichiometric run.

Mössbauer spectroscopy has also been used to examine ash samples from combustion tests on the original coal suite and the combustion tests conducted in the current contract period on Illinois #6, Beulah, and Loy Yang coals. These results are summarized in Table 4-79. All of the samples were obtained either from the Im1 specimens provided by the University of Arizona or the combustion tests conducted at SECV by PSIT, since these were the only ash samples with sufficient material to allow good Mössbauer spectra to be obtained, after CCSEM and XAFS specimens had been taken. A number of samples of Illinois #6 ash were analyzed, including the Illinois #6 coal ash from the original coal suite, and several samples of ash from the parent and product coal derived from SOAP cleaning. For the original ash sample (21-7-11-Im1-A), only 16% of the iron was incorporated into an aluminosilicate glass phase in a ferric valence state, with the balance of the iron (84%)

ending up as magnetite. The three runs on the SOAP parent Illinois #6 coal, yielded less iron as magnetite (62-68%), and more incorporated into glass (32-38%). Two of the samples (47D and 47H) exhibited both ferrous and ferric glass, while 47B contained only ferric glass, presumably reflecting combustion stoichiometry conditions. The ash from the SOAP product coal was much different, as expected. The major iron-bearing phase was a fine particle, superparamagnetic iron oxide phase, derived from the small included pyrite particles remaining in the coal after SOAP cleaning. A nonmagnetic ferric phase was also observed containing 23% of the iron, which could represent either iron in glass or a nonmagnetic component of the superparamagnetic ferric oxide. It should be noted that it is sometimes difficult to distinguish between a nonmagnetic ferric oxide and ferric iron contained in an aluminosilicate glass. This is also the situation for the Loy Yang ash samples in Table 4-79. The ferric glass component could well be a nonmagnetic ferric oxide, on the basis of its Mössbauer parameters. The ferric glass components of the other Illinois #6 ashes, the Beulah ashes, the Upper Freeport ashes, and the Kentucky #11 ashes exhibit larger quadrupole splitting and peak widths, characteristic of glass phases. Spectra obtained at cryogenic temperatures could resolve this point for the Illinois #6 SOAP ash and the Loy Yang ashes. Figure 4-106 shows the room temperature spectra of the Loy Yang and Beulah ash probe samples obtained during the SECV tests.

4.5.8 XAFS Spectroscopy Results

XAFS spectroscopy has been employed for several purposes in this study. First it has routinely been used to characterize the structure of calcium and potassium in the ashes produced in this investigation. Second, in situ XAFS studies of the reactions of calcium, potassium, iron and other elements have been conducted in a static environment to demonstrate the feasibility and potential of future, dynamic, in situ XAFS experiments. Finally, the capability of XAFS spectroscopy to speciate the forms of occurrence of critical trace elements in coals and ashes has been demonstrated.

Detailed analysis of the Phase I coal and ash samples was reported in the Phase I Final Report (Boni et al., 1990) and is not repeated herein. Only analytical data collected during Phase II are presented.

4.5.8.1 XAFS Spectroscopy Results Ca model compounds

XANES for six Ca model compounds (CaCO_3 , CaSO_4 , CaO , CaSiO_3 and two Ca-silicate glasses) are shown in Figure 4-107. A small peak below the edge is assigned to the $1s \rightarrow 3d$ transition and a shoulder on the rising part of the edge is assigned to the $1s \rightarrow 4p$ transition. The intensity (area of the peak) of the 3d peak is very sensitive to the site symmetry. It increases as the degree of the symmetry for the Ca site decreases. CaO contains regular octahedral CaO_6 units, and no $1s \rightarrow 3d$ transition peak is observed. For the other model compounds, the site symmetry for Ca ion is lower, and the $1s \rightarrow 3d$ transition peak is usually observed. Above the edge, several peaks were labeled as a, b, and c in the XANES (Figure 4-108). These peaks are due to the multiple scattering resonance (MSR) between the photoelectron excited by X-ray absorption and the coordination shells

surrounding the central absorbing atom. The position and intensity of these peaks depends on bond length, site symmetry, and type of the atoms in the neighboring shells. The XANES for the glass samples shows less distinct features. This is due to the fact that in a glass sample, the bond length has a broad distribution, thus the corresponding MSR peak (peak b) is smeared. These changes in the XANES for Ca-silicate glasses as compared with the corresponding crystallized Ca-silicates phase have been previously reported (Combes et al., 1991). The XANES features are usually used as fingerprints to qualitatively identify phases.

Radial structure functions (RSF) derived by Fourier transformation of the EXAFS for the model compounds are shown in Figures 4-108 and 4-109. The spectra for all the model compounds features a prominent peak at 2Å, corresponding to one or several oxygen shells at 2.4-2.5Å. As shown in the figure, the RSF features beyond the first oxygen shell(s) are very different from each other, providing important structural information for the samples. Less distinct features are shown for the Ca-silicate glass samples due to lack of long range order in the glasses. The actual distances and coordination numbers of the coordination shells represented by the peaks in RSF that are indicated in the figure can be determined by least squares analysis of the back transform of the peak or peaks in question (Teo, 1981).

4.5.8.2 Sucrose Chars Containing Ca Prepared by MIT

- 2a. MIT-10, dispersed Ca + SiO₂, synthetic char, unburned.
- 2b. MIT-2, dispersed Ca + SiO₂, synthetic char, probe - 2 in. - 0.9s
- 2c. MIT-4, dispersed Ca + SiO₂, synthetic char, probe - 3.5 in. - 0.16s
- 2d. MIT-6, dispersed Ca + SiO₂, synthetic char, probe - 5 in. - 0.23s.

The XANES spectra for these samples shown in Figure 4-110, were discussed previously, in a qualitative manner (Helble et al., 1992).

The Ca K-edge XANES for the unburned char indicates that the calcium is highly dispersed in a form similar to that observed for carboxyl-bound calcium in lignite (Huffman and Huggins, 1984), consistent with the loading technique, treatment of sucrose char with a calcium acetate solution. As the reaction time increases from 0.09 to 0.23s, a second b peak emerges, suggesting the formation of a crystallized phase. The splitting of the two b peaks is found to be 5.0 eV, close to that for CaSiO₃ (5.2 eV). The corresponding b peak splitting for CaO is 4.2 eV. A prominent peak c is seen in the XANES for all four samples. However, it is not seen in the XANES for CaSiO₃, suggesting that CaSiO₃ is not the only phase present.

The EXAFS RSF for the CaSiO₃ shows three distinct coordination shells at ~ 3.35, 5.2 and 6.7Å, respectively (Figure 4-111). Usually, the peaks in EXAFS RSF beyond 6 to 7Å cannot be assigned to a specific coordination shell because the signal is weak and the coordination shells at larger distance are not well separated. However, if atoms in a particular shell (shell a) are aligned with the central absorbing atom and the atoms in another shell (shell b) which locates between shell a and the central absorbing atom, the magnitude of

RSF for shell a will be enhanced due to multiple-scattering of the photoelectron with the neighboring shells of the central absorbing atom (Teo, 1981). Crystallographic data for CaSiO_3 shows that Ca has a Ca neighbor shell at 3.65Å and another Ca neighbor shell at 7.30Å. The atoms in the 7.30Å shell are aligned with the central absorbing atom and the atoms in the 3.65Å shell. EXAFS RSF for the 0.16 and 0.23s residence time samples shows two distinct peaks at 3.2 and 6.8Å. Least squares analysis of these two peaks reveals that they arise from two Ca shells 3.60 and 7.24Å, from the central Ca atom, respectively. The strong peak at 6.8Å also indicates that the CaSiO_3 phase is well crystallized, consistent with the XANES results.

4.5.8.3 New MIT samples

- 3a. Raw sample, MIT #21 (CAMIT21.470)
- 3b. MIT #1, CAI (complete B.O) 1650 K, 20% O_2 , 90/106 m.(CAMIT.462, 1991)
- 3c. MIT #4, CAI (C) 1650 K, 20% O_2 , 75/90m (CAMIT.465, 1991)
- 3d. MIT #6, CAI (C), 1350 C, 20% O_2 , 75/90m (CAMIT.469, 1991).

For the initial sample, Ca is again present in a highly dispersed form similar to carboxyl-bound Ca in lignite, on the basis of the XANES (Figure 4-112). The XANES for samples 3b, 3c, 3d (Figure 4-83) are almost identical to each other, showing a second weak b peak. The EXAFS RSF for samples 3c and 3d (Figure 4-113) again exhibit two peaks at 3.2 and 6.8Å, similar to CaSiO_3 . These peaks are much less distinct than those for the previous set of chars, however.

4.5.8.4 Ca XAFS Results for Ash Samples

In previous reports and papers (Helble et al., 1992; Helble, et al., 1992; Shah et al., 1991), we have reported that the Ca K-edge XANES spectra of most of the ash samples collected in combustion experiments at UA and PSIT indicate that the dominant Ca-containing constituent of the ash is Ca-aluminosilicate glass. This remains true for most of the samples we have examined. However, there are numerous examples where important secondary phases are observed as well.

As discussed previously (Helble et al., 1992; Helble et al., 1992; Shah et al., 1992) and illustrated by the data in this report, CCSEM results indicate that the Ca-Si-Al glass phase in the impactor 1 samples collected in the UA tests, which represent the ash of largest particle size, covers a broad composition range and includes many Ca-rich particles. The impactor 3 through 7 samples, which are smaller in particle size, have Ca-Si-Al phases with tighter, more glass-like compositions. It seems likely that the Ca-rich particles represent unreacted or partially reacted CaO particles formed from the carboxyl-bound calcium in low-rank coals or calcite in bituminous coals. Previously, however, analysis of the XAFS data has not clearly indicated a CaO phase for the impactor 1 samples.

In Figure 4-114, the Ca XANES spectra of some typical low-rank coal ash samples are compared. It is evident that the impactor 3 and 5 samples are essentially identical to

each other and to the Ca-aluminosilicate glass standard XANES shown in Figure 4-115. The impactor 1 XANES spectra in Figure 4-114 are also similar to the Ca-aluminosilicate glass XANES; however, the b peak region is enhanced in intensity and broadened, and the s→p transition peak is also somewhat enhanced. Both changes are consistent with the presence of some CaO.

The RSF for the impactor 1 samples (Figure 4-115) also exhibit evidence for CaO. The strong peak at 3.1Å is most likely due to the first Ca neighbor shell in CaO. Least squares analysis of the back transform of this peak gives a Ca shell distance of 3.42 Å, very close to the known value of 3.40Å for the first Ca shell in the CaO structure.

4.5.8.5 XAFS Results for Ash Samples from Ion-Exchanged Beulah Lignite and a Series of Samples from MIT.

The Ca XANES for ash from the Beulah parent coal and the ion-exchanged coal are shown in Figure 4-116. The XANES for the 3s RT DTF samples are very similar to the XANES of Ca-aluminosilicate glass, with indications of some CaO. For the 1s RT DTF samples, both the XANES and the RSF indicate a mixture of Ca-aluminosilicate and CaSO₄.

XANES for five K model compounds, K₂CO₃, K₂SO₄, K₂SiO₃, KAl₂Si₂O₆ (leucite) and KAlSi₃O₈ (feldspar) are shown in Figure 4-119. The splittings for a, b peaks, ΔE_{a,b} are 5.5 eV (K₂CO₃), 6.5 eV (K₂SO), 3.6 eV (K₂SiO₃), 3.9 eV (KAl₂Si₂O₆) and 4.0 eV (KAlSi₃O₈), respectively. In Figure 4-118, the XANES of 3s RT and the 1s RT ash from the Beulah potassium ion-exchanged lignite are compared to the XANES of K₂SO₄. Also shown is the potassium XANES from a sample obtained from MIT. It is seen that all of the XANES match rather closely. This is also true for the RSF derived from the EXAFS, several of which are compared in Figure 4-119. From these spectra it is clear that K₂SO₄ dominates the XAFS spectra of the K ion-exchanged Beulah ash samples, even though the CCSEM measurement indicates that more K is contained in aluminosilicate glass phases. In part, this is due to the fact that crystalline phases exhibit stronger, more characteristic XANES and RSF features than amorphous phases. It could also indicate a tendency for the K₂SO₄ to coat the surfaces of the ash particles.

The MIT series, MIT #7 - MIT #10 all clearly exhibit the XANES characteristic of K₂SO₄ (Figure 4-120). Since we were provided with very little information on these samples, however, we have not attempted any further interpretation or analysis.

4.5.8.6 In-situ high temp XAFS

Emphasis was placed on development and construction of a new furnace for static (i.e., captive particle sample) *in situ* high-temperature XAFS spectroscopy at the National Synchrotron Light Source (NSLS) at Brookhaven National Laboratory. The principal changes from the old design are (1) addition of Duraboard (an Al-Si oxide material) insulation, (2) additional water cooling of the cell and ion chamber, (3) molybdenum sample block and heaters, (4) a boron nitride sample boat and (5) an improved temperature

controller. The sample is put in the BN boat which is laid on its side without cover so that there is no attenuation due to window material. The behavior of potassium, calcium, iron and chlorine in ash and coal have been investigated under static in situ conditions as a function of temperature using this in situ XAFS furnace.

(1) Chlorine Release from Coal

In situ XAFS experiments were performed on two different samples of high chlorine Illinois #6 coal at temperatures up to 350°C. As the project sample of Illinois #6 coal is low in chlorine, the experiments were performed on alternate samples of this coal seam: one coal, obtained originally from the Illinois State Geological Survey, contained 0.84 wt% chlorine; the other coal contained 0.32 wt% chlorine. The initial chlorine XANES signatures of these two coals were very similar, not only to each other, but also to virtually all other chlorine-rich coals we have measured. Upon heating, the XANES signature sample of the Illinois #6 with the lower content of chlorine does not appear to change significantly, but remains similar to that of chloride anions surrounded by water molecules. The changes appear to be limited to reduction in the relative amplitude of the smaller peak at about 20 eV above the edge. The step-height parameter, which, to a first approximation, is proportional to the chlorine abundance, begins to decrease significantly above 200°C, and indicating that the chlorine is being removed from the coal at a rate much faster than the loss of the carbon/hydrogen matrix. The chlorine is probably being released as HCl, as other investigators have found. In contrast, the XANES spectrum of the sample with the higher amount of chlorine does change significantly with increasing temperature, indicating the formation of NaCl at the expense of the hydrous chloride anions. As temperature increases, the NaCl form begins to dominate the spectrum as more hydrous chloride anions are converted to NaCl and/or the hydrous chloride anions are released from the coal matrix. The reduction in the chlorine edge step-height parameter is much less for this coal indicating the stability of this NaCl form in the matrix at these temperatures.

Such results have implication for the release of chlorine during coal combustion. The major hydrous chloride form is released easily at temperatures below 400°C, whereas any chlorine present as NaCl presumably would not volatilize until much higher temperatures are reached. Hence, the different forms-of-occurrence of chlorine may have to be taken into account in thermodynamic/kinetic modelling of vaporous species associated with coal combustion.

(2) KOH/Kaolinite mixture

To study the high temperature interaction of clays and potassium species present in the coals, a 20% KOH - 80% kaolinite mixture was examined. Figure 4-121 shows potassium K edge XANES at different temperatures for the KOH/kaolinite mixture. In this mixture, which was prepared long before the actual XAFS experiment, KOH had reacted with CO₂ in the air to form K₂CO₃, which is readily recognized from the characteristic split peak at room temperature. On heating to 500°C, the XANES spectra show that potassium is quite reactive and reacts readily with kaolinite forming an amorphous aluminosilicate similar

to those normally observed in high temperature ashes. Further heating of the sample up to 800°C did not show much further change in the XANES spectra. After the experiment, the synthetic mixture sample looked like sponge cake in which sintering had caused the particles to adhere to each other.

(3) Ca(OH)_2 /Kaolinite mixture

The Ca(OH)_2 /kaolinite results are summarized in Figure 4-122. These spectra show no significant reaction between the oxide/hydroxide phase and the kaolinite up to 700°C, at which temperature all of the hydroxide has been converted to CaO. Whereas the spectrum at 700°C is highly characteristic of CaO, however, the spectrum at 800°C shows virtually no features that can be attributed to CaO and appears similar to spectra of Ca aluminosilicates that we have measured previously. This would appear to imply that the reaction of CaO with kaolinite is negligible at 700°C, but is relatively rapid at 800°C with respect to the time-frame of the approximately 60-min interval between spectral measurements.

(4) Magnetite/pyrrhotite mixture

To study the transformation of Fe-bearing phases at the high temperatures of coal combustion, three ash samples from the PSIT drop tube experiments on hydrothermal pyrite were combined into a single sample. These three samples of ashes had been made from pyrite with residence times varying from 670 to 906 ms at 1500 K and 3% oxygen atmosphere. The constitution of the mixed sample averaged about 3% hematite, 45% magnetite and 47% pyrrhotite based on results from Mössbauer spectroscopy. The sample was diluted by mixing it with boron nitride powder. Figure 4-123 shows a series of in-situ Fe K-edge XANES at different temperatures. As the temperature increases, the Debye-Waller factor increases and the XANES spectra start to lose some of their features. However, up to 1100°C, there is little change in the Fe XANES. At 1200°C, the Fe XANES is virtually featureless. On cooling to room temperature, the spectrum becomes more defined and resembles the XANES spectrum of iron metal. After the run, Mössbauer analysis established that the sample contained 46% of its iron in troilite (FeS) and 54% as iron metal.

The signal-noise ratio for the XAFS data was sufficient to obtain radial structure functions (RSFs) from most of the high-temperature spectra. The RSF are shown in Figure 4-124 and demonstrate the loss of the 2nd nearest neighbor shell in the iron oxide and sulfide structure with increasing temperature. At 1100°C, this peak is absent. We speculate that the disappearance of this peak is related to increasing disorder (melting at temperatures above 1000°C).

It appears that the molybdenum metal used in the furnace cell assembly acted as an oxygen getter and reduced the partial pressure of oxygen in the XAFS furnace cell so that iron oxide was reduced to metallic iron. This was evident from both the XAFS and Mössbauer results obtained from this sample after cooling to room temperature following the in situ experiment. This result means that we will have to take precautions to ensure the correct oxygen fugacity in the cell in future experiments.

4.5.8.7 XAFS Studies of Trace Elements in Coal and Ashes

Recently, we have initiated XAFS studies of critical trace elements in coals and ashes. These studies, which have been published in a preliminary form (Huggins et al., 1992; Helble et al., 1992c), establish that XAFS is a viable technique for investigation of the form of occurrence of trace elements in the 10 to 100 ppm range. A brief description of some of the results follows.

For chromium in coal, XAFS studies of bituminous coals and combustion ashes generated at PSIT have established that 1) the chromium form of occurrence is similar in different bituminous coals, although the specific form of occurrence has not as yet been identified; 2) the chromium oxidation state is Cr^{3+} and not the much more toxic Cr^{6+} ; 3) chromium is not present as chromite (FeCr_2O_4), which has been considered by geochemists to be the most likely form of occurrence of chromium in coals; and 4) chromium remains as Cr^{3+} and is not oxidized to Cr^{6+} in combustion ash.

For arsenic, similar XAFS studies have established that 1) the arsenic in coal that is associated with pyrite occurs by substituting for sulfur and not as the separate mineral arsenopyrite (FeAsS); 2) arsenic can be readily oxidized to arsenate complexes (AsO_4^{3-}); and 3) arsenate complexes are found in coal slags. In some coal samples, at least half of the arsenic is oxidized to arsenate under conditions of storage at ambient conditions. The XANES spectra of several Upper Freeport coal fractions and bottom ash from a UA combustion test are shown in Figure 4-125. The s→p transition peaks from As in pyrite and arsenate are labeled P and A, respectively. These studies have established that the potentially leachable arsenate form is easily formed by oxidation under ambient conditions and during combustion.

4.6 References

Boni, A.A. et al., "Transformations of Inorganic Coal Constituents in Combustion Systems," Phase I Final Report submitted to DOE/PETC under Contract DE-AC22-86PC90751, March (1990).

Combes, J.-M., Brown, G.E. Jr., and Waychunas, G.A., in X-Ray Absorption Fine Structure (Eds. S. Samar Hasnain), p. 312-314, Ellis Horwood, New York (1991).

Helble, J.J., Srinivasachar, S., Boni, A.A., Kang, S.G., Graham, K.A., Sarofim, A.F., Beer, J.M., Gallagher, N.B., Bool, L.E., Peterson, T.W., Wendt, J.O.L., Shah, N., Huggins, F.E., and Huffman, G.P., "Mechanisms of Ash Evolution - A Fundamental Study Part I: Low Rank Coals and the Role of Calcium," Proceedings, Engineering Found. Conf., "Inorganic Transformations and Ash Deposition During Combustion," Palm Coast, FL, Ed., Benson, S.A.; pp. 209-229 (1992a).

Helble, J.J., Srinivasachar, S., Boni, A.A., Kang, S.G., Graham, K.A., Sarofim, A.F., Beer, J.M., Gallagher, N.B., Bool, L.E., Peterson, T.W., Wendt, J.O.L., Shah, N.,

Huggins, F.E., and Huffman, G.P., "Mechanisms of Ash Evolution - A Fundamental Study Part I: Low Rank Coals and the Role of Calcium," Proceedings, Engineering Found. Conf., "Inorganic Transformations and Ash Deposition During Combustion," Palm Coast, FL, Ed., Benson, S.A.; pp. 229-248 (1992b).

Helble, J.J., Huggins, F.E., Senior, C.L., Srinivasachar, S., Shah, N., and Huffman, G.P., "The Fate of Chromium During Pulverized Coal Combustion," Proc. Ninth Annual Int'l Pittsburgh Coal Conference (1992c).

Helble, J.J. et al., "Transformations of Inorganic Coal Constituents in Combustion Systems," Quarterly Report No. 19 submitted to DOE/PETC under Contract DE-AC22-86PC90751, September (1991).

Huffman, G.P. and Huggins, F.E., Fuel 57, 592 (1978).

Huffman, G.P., Huggins, F.E., and Dunmyre, G.R., Fuel 60, 585-597 (1981).

Huffman, G.P. and Huggins, F.E., "Analysis of the Inorganic Constituents in Low-Rank Coals," ACS Symposium Series No. 264, pp. 159-174, Chemistry of Low-Rank Coals, Ed., H.H. Schobert, Amer. Chem. Soc. (1984).

Huffman, G.P., Huggins, F.E., Shoenberger, R.A., Walker, J.S., Greegor, R.B., and Lytle, F.W., Fuel 65, 621-632 (1986).

Huffman, G.P., Huggins, F.E., and Shah, N., "Behavior of Basic Elements During Coal Combustion," Progress in Energy and Combustion Science, 16, #4, 293-302 (1990).

Huffman, G.P., Huggins, F.E., Levasseur, A.A., Durant, J., Lytle, F.W., Greegor, R.B., and Arun Mehta, Fuel, 68, 238-242 (1989).

Huffman, G.P., Mitra, S., Huggins, F.E., Shah, N., Vaidya, S. and Lu, F. Energy & Fuels, 5, 574-581 (1991).

Huggins, F.E., Kosmack, D.A., Huffman, G.P., and Lee, R.J., "Coal Mineralogies by SEM Automatic Image Analysis," Scanning Electron Microscopy/I, 531-540, SEM Inc., AMF O'Hare, Chicago, IL 60666, USA (1980).

Huggins, F.E., Huffman, G.P., and Lee, R.J., "Scanning Electron Microscopy-Based Automatic Image Analysis (SEM-AIA) and Mössbauer Spectroscopy: Quantitative Characterization of Coal Minerals," ACS Symposium Series No. 205, pp. 239-258, Coal and Coal Products: Analytical Characterization Techniques, Ed., E.L. Fuller, Jr., American Chemical Society (1982).

Huggins, F.E., Shah, N., Zhao, J., and G.P. Huffman, "Application of XAFS Spectroscopy to the Speciation of Critical Trace Elements in Coal Utilization," Amer. Chem. Soc. Div. of Fuel Chem. Preprints, 37(3), 1110-1116 (1992).

Lee, R.J., Huggins, F.E., and Huffman, G.P. "Correlated Mössbauer-SEM Studies of Coal Mineralogy, Vol. 1, 561-568, SEM Inc., AMF O'Hare, IL (1978).

Levin, E.M., Robbins, C.R., and McMurdie, H.F., "Phase Diagrams for Ceramists, Vol. I," The Amer. Ceramic Soc. (1964).

Shah, N., Huffman, G.P., Huggins, F.E., and Shah, A. "Reaction of Calcium and Alkali Elements with Aluminosilicates and Quartz During Coal Combustion," Proceedings, 1991 International Conference on Coal Science, Newcastle, England, Ed., Int. Energy Agency, Butterworth-Heinemann Ltd., 404-407 (1991).

Shah, N., Huffman, G.P., Huggins, F.E. and Shah, A., "Graphical Representation of CCSEM Data for Coal Minerals and Ash Particles," Proceedings, Eng. Fd. Conf., "Inorganic Transformation and Ash Deposition," Palm Coast, FL,; Ed., Benson, S.A.; pp. 179-190 (1992).

Srinivasachar, S., Helble, J.J., Boni, A.A., Huffman, G.P., Huggins, F.E., and Shah, N., "Mineral Behavior During Coal Combustion: 2. Illite Transformations," Progress in Energy and Combustion Science, 16, #4, 243-252 (1990).

Teo, B-K., J. Am. Chem. Soc. 103, 3990 (1981).

TABLE 4-1. - Mössbauer data - raw coals

% Fe in:	Upper Freeport	W. Ken- tucky #9	W. Ken- tucky #11	Illinois #6	Beulah Lignite	Eagle Butte	San Miguel
Pyrite	79	97	98	> 99	100	(100)*	100
Siderite	7						
Fe ²⁺ in clays	11	3	2	< 1			
Jarosite	3						
Wt% pyritic sulfur	1.42	2.33	3.92	1.48	0.60	< 0.07	0.50
*Absorption very weak; could include some oxyhydroxide and/or jarosite.							

TABLE 4-2. - Mineralogical data - raw coals

Mineral	Upper Freeport		W. Kentucky #9		W. Kentucky #11		Illinois #6		Beulah Lignite		Eagle Butte		San Miguel	
	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal	Wt% MM ¹	Wt% Coal
Quartz	10	2.1	12	1.9	19	4.7	20	2.0	12	1.2	40	1.8	12	6.5
Kaolinite	7	1.4	6	0.9	8	2.0	6	0.6	30	3.1	13	0.6	2	1.1
Illite	35	7.2	23	3.6	16	3.9	10	1.0	1	0.1	2	0.1	-	-
Chlorite	1	0.2	-	-	-	-	<1	-	-	-	-	-	-	-
Montmorillonite	1	0.2	<1	-	1	0.2	<1	-	1	0.1	2	0.1	16	8.7
Mixed silicates	19	3.9	34	5.4	23	5.6	18	1.8	13	1.3	16	0.7	64	34.7
Pyrite	18	3.7	16	2.5	24	5.9	28	2.8	26	2.6	4	0.2	2	1.1
Jarosite	<1	<0.2	-	-	-	-	-	-	3	0.3	-	-	-	-
Fe2 + sulfates	-	-	<1	-	<1	-	2	0.2	2	0.2	<1	-	-	-
Gypsum	-	-	-	-	1	0.2	1	0.1	-	-	-	-	-	-
Fe-rich minerals	1	0.2	-	-	<1	-	1	0.1	<1	<0.1	4	0.2	-	-
Ca-rich minerals	2	0.4	3	0.3	4	1.0	7	0.7	1	0.1	3	0.1	-	-
Ti-rich minerals	<1	<0.2	<1	-	-	-	-	-	-	-	1	0.0	-	-
Apatite	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Miscellaneous, mixed	6	1.2	4	0.8	3	0.7	7	0.7	10	1.0	15 ³	0.7	4	2.2
	100	20.5	100	15.8	100	24.5	100	9.9	100	10.0 ²	100	4.5 ²	100	54.2

¹Discrete Mineral Matter

²With allowance for dispersed components, CaO, MgO, Na₂O, that constitute approximately 25 to 30 wt% of the ash.

³Includes significant (2 to 3 wt%) Ca-Sr(Si)-Al-P mineral - crandallite?

TABLE 4.3. - Average discrete mineral species composition - Phase I coals

Mineral Species	Elemental Composition ^a											Wt%	ρ^s
	Na	Mg	Al	Si	S	Cl	P	K	Ca	Ti	Fe		
W. Kentucky #11 Coal													
Quartz			3	94				1		1		19	2.65
Kaolinite			40	51	3			2	2	2	2	8	2.62
Illite			28	54	3			10	1	2	4	16	2.65
Chlorite			27	35	5			1			31	< < 1	3.1
Montmorillonite	2		17	73	2	1		3	1	2	1	1	2.5
Misc. silicates			21	61	2			11	2	2	4	19	2.65
Gypsum			2	4	50			1	42	1	1	1	2.35
Fe2+ sulfate			1	5	42			1		2	48	< 1	2.5
Pyrite			2	3	63			1		1	33	24	5.0
Fe-rich (siderite)	1		6	13	9			1	1	1	69	< 1	4.0
Ca-rich (calcite)	1	1		1	2				89		1	4	2.75
Ti-rich (rutile)		1	6	10	3				1	77	2	< < 1	4.2
Sil/sul			18	40	27	2		8	2	1	5	3	2.5
Sil/pyr			14	41	20			7	4	1	12	1	3.5
Misc. mixed			11	30	11	4	3	6	14	17	6	2	2.5
Beulah Lignite													
Quartz				97	1				1	1		12	2.65
Kaolinite			42	52	2	1		1	1	1	1	30	2.62
Illite	1		34	50	1			8	2	1	3	1	2.65
Montmorillonite			20	66	4	1		2	5		1	1	2.5
Misc. silicates			30	57	3	1		2	3	2	2	13	2.65
Jarosite			3	6	39			8	3	3	39	3	3.2
Pyrite		1		1	66					2	31	26	5.0
Fe-rich (siderite)		3	4	8	3	2	1	2	4	2	69	< 1	4.0
Ca-rich (maceral)		3	4	3	13	1	1		71	1	4	1	2.75
Sil/Sul	1	1	26	39	14	1		4	9	2	2	< 1	2.5
Sul/pyr			32	22	17	7		10	1		10	< 1	3.5
Misc. mixed*	2	4	12	15	24	4	2	3	20	15	6	10	2.5

TABLE 4-3. - Average discrete mineral species composition - Phase I coals (Cont.)

Mineral Species	Elemental Composition ^a											Wt%	ρ^b
	Na	Mg	Al	Si	S	Cl	P	K	Ca	Ti	Fe		
W. Kentucky #9 Coal													
Quartz			3	93	1			1		1	2	12	2.65
Kaolinite			42	51	3	1		2	1	1	1	6	2.62
Illite	1		28	52	4	1		11	2	1	4	23	2.65
Montmorillonite	1		19	72	3			2	1	1		<1	2.5
Misc. silicates			18	63	3	1		9	2	2	5	22	2.65
Fe ₂ + sulfate			2	2	53					1	41	<1	2.5
Pyrite			2	2	61					1	34	16	5.0
Ca-rich (calcite)		1	1	2	3	1	1	1	88	1	1	3	2.75
Ti-rich (rutile)		1	6	10	3				1	77	2	<1	4.2
Sil/sul			17	42	28			6	3	2	3	12	2.5
Sil/pyr			15	36	24			6	2	1	14	1	3.5
Misc. mixed	1	2	14	21	14	10	4	4	14	6	11	4	2.5
Upper Freeport Coal													
Quartz			2	93				1	1	1	1	10	2.65
Kaolinite	1	1	38	49	2	3		2	2	1	1	7	2.62
Illite	1	1	28	51	1	2		12	2	2	3	35	2.65
Chlorite	2	4	21	36	2	1		1	2	1	31	1	3.1
Montmorillonite	1		20	71	2	1		2	1		2	1	2.5
Misc. silicates	1	1	20	57	2	1		7	1	2	10	18	2.65
Jarosite		1	6	11	44			6	1	3	26	<1	2.5
Pyrite		1	2	4	59				1	1	33	18	5.0
Fe-rich (siderite)		3	4	8	3	2	1	2	4	2	69	1	4.0
Ca-rich (calcite)		1	4	4	2			1	84	1	2	2	2.75
Ti-rich (rutile)	1	1	3	9	1			1		82	3	<1	4.2
Sil/sul	1	1	24	46	14	4		2	4	2	10	<1	2.5
Sil/pyr			6	12	43			2	17	2	10	1	3.5
Misc. mixed	1	3	13	30	12	8	2	9	7	10	10	5	2.5

TABLE 4-3. - Average discrete mineral species composition - Phase I coals (Cont.)

Mineral Species	Elemental Composition ^a											Wt%	ρ^b
	Na	Mg	Al	Si	S	Cl	P	K	Ca	Ti	Fe		
Eagle Butte Coal													
Quartz			1	96				1	1	1	1	40	2.65
Kaolinite	1		41	52	1	1		1	2	2	1	13	2.62
Illite			28	53	1	2		10	3	2	2	2	2.65
Montmorillonite			18	68	2			2	4	4	1	2	2.5
Misc. silicates	1	2	20	50	2	2		3	6	2	4	13	2.65
Fe2+ sulfate			1	2	55				1	1	40	<1	2.5
Pyrite				1	60				2		36	4	5.0
Fe-rich (siderite)			1	3	2		2	1	4	2	85	4	4.0
Ca-rich (calcite)	1		1	3	4	1	1	3	84	1	5	3	2.75
Ti-rich (rutile)		1		5	2	1		1	2	87	1	1	4.2
Sil/sul	1		25	50	8	3		1	9	4	0	2	2.5
Sil/pyr		o	14	56	4			5	14	3	2	<1	3.5
Misc. mixed	1	2	22	15	8	4	11	4	28	8	4	15 ⁺	2.5
Illinois #6 Coal													
Quartz				96	1			1		1	1	20	2.65
Kaolinite			41	51	4	1		1		1	1	6	2.62
Illite			28	50	5			13	1	1	2	10	2.65
Chlorite		5	21	36	2			1			35	<1	3.1
Montmorillonite	2		16	72	5			1	2	1	1	<1	2.5
Misc. silicates		1	21	61	2			10	2	2	4	18	2.65
Fe2+ sulfate			1	2	48				1	1	46	<1	2.5
Pyrite			1	1	65						32	28	5.0
Fe-rich (siderite)			1	4	9						82	1	4.0
Ca-rich (calcite)			1	1	2		1	1	91			7	2.75
Ti-rich (rutile)			3	4	7	1				82		<1	4.2
Apatite (Ca, P)			1	1			28	1	66	2	1	<1	3.2
Sil/sul	1	1	15	43	23	1		7		2	7	5	2.5
Sil/pyr			14	48	18	1		8	1	2	10	1	3.5
Misc. mixed	1	3	13	30	12	8	2	9	7	10	10	2	2.5

TABLE 4-3. - Average discrete mineral species composition - Phase I coals (Cont.)

Mineral Species	Elemental Composition ^a											Wt%	ρ^s
	Na	Mg	Al	Si	S	Cl	P	K	Ca	Ti	Fe		
San Miguel Lignite													
Quartz			3	92	1			2	1	1	1	12	2.65
Kaolinite			40	55	2			1	1	1	1	2	2.62
Montmorillonite [^]			16	71	2	1		3	3	2	1	16	2.5
Misc. silicates [^]			14	74	1			6	2		1	64	2.65
Pyrite			1	6	60				1	2	30	2	5.0
Sil/sul			12	63	16	2		1	6	2	1	3	2.5
Sil/pyr	1		9	48	21	1		3	4	1	12	<1	3.5
Misc. mixed [*]			10	38	13				16	21	2	1	2.5
<div>s - specific gravity of individual mineral species</div> <div>* - mostly from macerals richer than average in S or Ca</div> <div>+ - includes significant amount (up to 5 wt%) of Ca-Sr(Si)-Al-P mineral, possibly crandallite</div> <div>^ - mostly zeolites (see text)</div> <div>^a - normalized X-ray counts from CCSEM</div>													

TABLE 4-4. - Mössbauer data for coals used in new combustion runs

Sample	H (kG)	I.S. (mm/s)	Q.S. (mm/s)	% Fe	Phase	Pyritic Sulfur (wt%)
Beulah coal	—	0.32	0.63	100	Pyrite	0.64
Kentucky #9 coal	—	0.32	0.60	59	Pyrite	1.23
	—	0.36	1.16	31	Jarosite	
	—	1.34	2.87	10	FeSO ₄ ·7H ₂ O	
Illinois #6 Parent	—	0.32	0.58	47	Pyrite	0.35
	—	0.38	1.08	53	Jarosite	
Illinois #6 SOAP	—	0.36	0.58	29	FeOOH	
	—	0.38	1.12	71	Jarosite	
Eagle Butte (very weak Mössbauer spectrum)	—	0.37	0.76	100	FeOOH	
Loy Yang 1953 (very weak Mössbauer spectrum)	—	0.37	0.64	60	FeOOH	
	488	0.33	—	17	Superparamagnetic Fe Ox.	
	292	0.53	—	23	Superparamagnetic Fe Ox.	
Loy Yang 2301	Mössbauer spectrum too weak to analyze.					

TABLE 4-5. - Loy Yang 1953 in epoxy psi

SAMPLE #484 LOY YANG COAL 1953 in epoxy psi

RUN 1 DATE 26-FEB-92 SUMMARY 135 TOTAL 789

AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
182	Quartz	0.	0.	0.100.	0.	0.	0.	0.	0.	0.	0.	0.	23.1
1	Kaolinite	0.	0.	47. 44.	0.	0.	0.	3.	3.	0.	2.	0.	0.0
10	Illite	0.	0.	33. 54.	0.	1.	1.	9.	1.	0.	1.	0.	0.5
1	Montmorillonite	0.	0.	14. 71.	0.	3.	0.	0.	6.	0.	5.	0.	0.2
102	Misc. Silicates	0.	3.	12. 68.	0.	2.	0.	1.	2.	1.	9.	0.	7.8
1	Elem. Sulfur	0.	0.	0. 0.	0.	100.	0.	0.	0.	0.	0.	0.	0.3
51	Pyrite	0.	0.	0. 0.	0.	66.	0.	0.	0.	0.	33.	0.	5.8
6	Misc. sulf.	0.	0.	1. 3.	0.	36.	0.	0.	45.	8.	1.	0.	0.3
2	Sylvite	0.	0.	0. 0.	0.	2.	46.	49.	2.	0.	0.	0.	0.1
116	Fe-rich	0.	0.	0. 0.	0.	0.	0.	0.	0.	0.	100.	0.	42.5
3	Calcite	0.	0.	0. 0.	0.	1.	0.	0.	99.	0.	0.	0.	0.1
60	Mixed Carbonate	0.	3.	1. 4.	0.	11.	1.	0.	48.	0.	30.	0.	4.4
1	Ti oxide	0.	0.	0. 3.	0.	0.	0.	0.	0.	87.	10.	0.	0.1
3	Ti-rich	0.	0.	0. 5.	0.	5.	0.	0.	0.	90.	0.	0.	0.2
1	Quartz-Sulfate	0.	0.	0. 36.	0.	39.	0.	16.	0.	0.	9.	0.	0.0
2	Quartz-Pyrite	0.	0.	0. 64.	0.	21.	4.	0.	0.	0.	10.	0.	0.0
35	Alumina-rich	0.	0.	91. 4.	0.	2.	1.	1.	1.	0.	0.	0.	2.2
170	Misc. Mixed	1.	1.	2. 26.	1.	17.	8.	3.	37.	1.	2.	0.	12.4
747	GRAND TOTALS	0.	1.	3. 32.	0.	7.	1.	1.	7.	1.	47.	0.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Quartz	23.1	11.	20.	6.	10.	6.	15.	32.
Misc. Silicates	7.8	15.	31.	14.	4.	5.	14.	17.
Fe-rich	42.5	3.	9.	3.	9.	4.	8.	63.
Misc. Mixed	12.4	21.	59.	8.	10.	2.	0.	0.
MINOR MINERALS	14.2	51.	27.	10.	10.	3.	0.	0.

GRAND TOTALS	100.0	15.	22.	6.	9.	4.	8.	35.

TABLE 4-(a). - Beulah SECV/PSIT Coal

SAMPLE 592 BEULAH PSI COAL 3 2
 RUN 1 DATE 8-DEC-91 SUMMARY 104 TOTAL 1199
 AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
80	Quartz	0.	0.	0.100.	0.	0.	0.	0.	0.	0.	0.	0.	6.6
134	Kaolinite	0.	0.	47.	52.	0.	0.	0.	0.	1.	0.	0.	10.3
5	Illite	0.	0.	31.	50.	0.	1.	0.	12.	2.	0.	3.	0.4
1	Chlorite	0.	0.	19.	27.	0.	6.	0.	0.	7.	0.	41.	0.1
1	Montmorillonite	0.	0.	25.	69.	0.	2.	0.	0.	4.	0.	0.	0.1
122	Misc. Silicates	0.	0.	34.	54.	0.	2.	0.	1.	6.	0.	4.	10.2
85	Pyrite	0.	0.	0.	0.	0.	61.	0.	0.	0.	0.	38.	10.2
15	Ferrous Sulfate	0.	0.	0.	0.	0.	52.	0.	0.	0.	0.	48.	1.4
1	Jarosite	0.	0.	3.	5.	0.	39.	0.	5.	0.	0.	48.	0.0
26	Gypsum	0.	0.	0.	1.	0.	45.	0.	0.	53.	0.	1.	1.1
263	Misc. sulf.	0.	0.	2.	3.	0.	41.	0.	1.	33.	4.	16.	22.2
20	Fe-rich	0.	0.	0.	0.	0.	2.	0.	0.	3.	0.	95.	3.2
4	Calcite	0.	5.	0.	1.	0.	4.	0.	0.	83.	2.	3.	0.3
110	Mixed Carbonate	0.	1.	0.	2.	0.	14.	0.	0.	22.	0.	60.	10.7
1	Ti oxide	0.	0.	0.	0.	0.	0.	0.	0.	3.	97.	0.	0.1
9	Ti-rich	0.	0.	0.	2.	0.	40.	0.	0.	4.	54.	0.	1.2
1	Trace-rich	29.	0.	0.	0.	0.	7.	3.	0.	0.	0.	0.	0.1
1	Quartz-Sulfate	0.	0.	0.	45.	0.	38.	0.	0.	0.	5.	8.	0.5
3	Sil-sulf	0.	0.	32.	31.	0.	24.	3.	0.	10.	0.	0.	0.4
3	Silicate-Pyrite	0.	0.	14.	21.	0.	27.	0.	0.	2.	8.	28.	0.1
301	Misc. Mixed	0.	1.	10.	19.	0.	22.	1.	1.	34.	2.	9.	20.9
1186	GRAND TOTALS	0.	0.	11.	23.	0.	24.	0.	0.	18.	2.	20.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Kaolinite	10.3	9.	20.	17.	22.	12.	9.	11.
Misc. Silicates	10.2	27.	31.	19.	16.	2.	5.	0.
Pyrite	10.2	4.	0.	12.	28.	19.	32.	4.
Misc. sulf.	22.2	11.	6.	31.	36.	8.	5.	3.
Mixed Carbonate	10.7	4.	10.	40.	35.	7.	5.	0.
Misc. Mixed	20.9	12.	10.	35.	37.	4.	1.	0.
MINOR MINERALS	15.4	6.	17.	22.	29.	11.	7.	8.
GRAND TOTALS	100.0	10.	12.	27.	31.	9.	8.	3.

TABLE 4-6(b). - Beulah SECV/PSIT Coal (Cont)

SAMPLE 592 PSI BEULAH COAL 3 2
 RUN 1 DATE 9-DEC-911 SUMMARY 108 TOTAL 1199
 AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
88	Quartz	0.	0.	0.	98.	0.	0.	0.	0.	1.	0.	0.	8.8
168	Kaolinite	0.	0.	46.	53.	0.	0.	0.	0.	1.	0.	0.	15.3
20	Illite	0.	0.	25.	52.	0.	5.	0.	14.	0.	0.	4.	1.4
1	Chlorite	0.	0.	18.	29.	0.	6.	0.	0.	0.	0.	47.	0.1
2	Montmorillonite	0.	0.	20.	69.	0.	3.	0.	0.	5.	0.	2.	0.1
130	Misc. Silicates	0.	0.	34.	57.	0.	2.	0.	1.	4.	0.	2.	14.2
92	Pyrite	0.	0.	0.	0.	0.	60.	0.	0.	0.	0.	40.	10.1
25	Ferrous Sulfate	0.	0.	0.	0.	0.	50.	0.	0.	0.	0.	50.	1.3
5	Jarosite	7.	0.	0.	3.	0.	33.	0.	5.	4.	0.	46.	0.2
20	Gypsum	0.	0.	0.	0.	0.	45.	0.	0.	54.	0.	0.	1.5
277	Misc. sulf.	0.	0.	1.	4.	0.	38.	0.	1.	35.	3.	18.	24.6
10	Fe-rich	0.	0.	0.	0.	0.	2.	0.	0.	2.	0.	95.	0.7
1	Calcite	0.	0.	0.	4.	0.	4.	0.	0.	92.	0.	0.	0.0
75	Mixed Carbonate	0.	0.	1.	4.	0.	13.	0.	0.	28.	0.	54.	4.8
2	Ti oxide	0.	0.	0.	0.	0.	3.	0.	0.	9.	88.	0.	0.2
18	Ti-rich	0.	0.	0.	2.	0.	37.	0.	0.	2.	58.	1.	1.6
1	Trace-rich	21.	0.	0.	0.	0.	7.	3.	0.	0.	0.	0.	0.1
3	Quartz-Pyrite	0.	0.	5.	34.	0.	23.	0.	4.	0.	0.	33.	0.2
4	Silicate-Pyrite	0.	0.	14.	25.	0.	23.	0.	0.	8.	0.	30.	0.1
246	Misc. Mixed	0.	1.	9.	23.	0.	20.	2.	0.	30.	1.	12.	14.8
1188	GRAND TOTALS	0.	0.	14.	30.	0.	21.	0.	1.	16.	2.	15.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Quartz	8.8	15.	45.	11.	7.	10.	0.	
Kaolinite	15.3	5.	42.	18.	9.	4.	3.	
Misc. Silicates	14.2	19.	46.	11.	14.	2.	5.	2.
Pyrite	10.1	3.	4.	12.	14.	25.	20.	21.
Misc. sulf.	24.6	18.	41.	10.	10.	9.	6.	5.
Misc. Mixed	14.8	26.	45.	20.	5.	3.	1.	0.
MINOR MINERALS	12.2	23.	16.	20.	14.	14.	13.	0.
GRAND TOTALS	100.0	16.	36.	14.	12.	9.	7.	4.

TABLE 4-6(c). - Beulah SECV/PSIT Coal (Cont)

SAMPLE 592 PSI BEULAH COAL 3 2
 RUN 1 DATE 10-DEC-91 SUMMARY 112 TOTAL 1199
 AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
88	Quartz	0.	0.	0.	99.	0.	0.	0.	0.	0.	0.	0.	6.4
155	Kaolinite	0.	0.	46.	52.	0.	0.	0.	0.	1.	0.	0.	11.8
5	Illite	0.	0.	27.	54.	0.	4.	0.	12.	0.	0.	3.	1.2
2	K-Feldspar	0.	7.	14.	41.	0.	0.	0.	19.	3.	1.	15.	0.2
1	Chlorite	0.	0.	16.	29.	0.	4.	0.	0.	4.	0.	46.	0.1
5	Montmorillonite	1.	0.	23.	65.	0.	3.	0.	1.	6.	0.	1.	0.4
209	Misc. Silicates	0.	0.	35.	55.	0.	3.	0.	0.	5.	0.	2.	14.6
75	Pyrite	0.	0.	0.	0.	0.	60.	0.	0.	0.	0.	40.	12.5
24	Ferrous Sulfate	0.	0.	0.	0.	0.	51.	0.	0.	0.	0.	49.	1.8
1	Jarosite	0.	0.	0.	0.	0.	43.	0.	8.	0.	0.	49.	0.1
24	Gypsum	0.	0.	0.	1.	0.	45.	0.	0.	53.	0.	0.	1.5
244	Misc. sulf.	0.	0.	1.	2.	0.	40.	0.	1.	39.	6.	10.	21.6
13	Fe-rich	0.	0.	0.	0.	0.	2.	0.	0.	2.	0.	95.	1.6
2	Calcite	0.	9.	0.	0.	0.	8.	0.	0.	70.	0.	8.	0.0
88	Mixed Carbonate	0.	1.	1.	3.	0.	14.	0.	0.	38.	1.	42.	6.0
1	Ti oxide	0.	0.	0.	4.	0.	4.	0.	0.	7.	85.	0.	0.0
18	Ti-rich	0.	0.	0.	1.	0.	33.	0.	0.	2.	63.	1.	3.3
1	Quartz-Sulfate	0.	0.	0.	23.	0.	59.	0.	0.	10.	4.	0.	0.1
1	Quartz-Pyrite	0.	0.	0.	23.	0.	40.	0.	0.	0.	0.	36.	0.0
234	Misc. Mixed	0.	1.	9.	16.	0.	22.	1.	1.	39.	3.	7.	16.8
1191	GRAND TOTALS	0.	0.	13.	25.	0.	24.	0.	1.	19.	4.	14.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Kaolinite	11.8	11.	10.	21.	22.	11.	22.	2.
Misc. Silicates	14.6	41.	24.	16.	10.	5.	4.	0.
Pyrite	12.5	1.	5.	11.	18.	18.	16.	32.
Misc. sulf.	21.6	11.	6.	29.	35.	11.	7.	1.
Misc. Mixed	16.8	15.	24.	30.	26.	4.	2.	0.
MINOR MINERALS	22.7	11.	22.	23.	13.	12.	13.	7.

GRAND TOTALS	100.0	15.	15.	23.	21.	10.	10.	6.

TABLE 4-7. - PSIT Illinois #6 parent coal in epoxy (for SOAP #485)

SAMPLE # 492 PSI ILLINOIS #6 PARENT COAL IN EPOXY(FOR SOAP #485)

RUN 1 DATE 1-MAY-91 SUMMARY 124 TOTAL 1199

AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
252	Quartz	0.	0.	0.	98.	0.	1.	0.	1.	0.	0.	0.	19.8
62	Kaolinite	0.	0.	47.	51.	0.	0.	0.	0.	0.	0.	0.	4.5
73	Illite	0.	0.	28.	53.	0.	4.	0.	11.	0.	0.	3.	7.4
9	K-Feldspar	0.	0.	16.	51.	0.	7.	0.	19.	0.	0.	6.	0.9
2	Chlorite	0.	0.	19.	32.	0.	8.	0.	0.	0.	0.	42.	0.0
317	Misc. Silicates	0.	0.	20.	59.	0.	8.	0.	5.	0.	0.	6.	28.7
121	Pyrite	0.	0.	0.	0.	0.	61.	0.	0.	0.	0.	38.	13.8
34	Ferrous Sulfate	0.	0.	0.	0.	0.	50.	0.	0.	0.	0.	49.	1.8
9	Jarosite	0.	0.	0.	3.	0.	38.	0.	7.	0.	0.	52.	0.5
4	Gypsum	0.	0.	0.	0.	0.	46.	0.	0.	54.	0.	0.	0.2
110	Misc. sulf.	0.	0.	0.	6.	0.	38.	0.	1.	3.	0.	50.	10.7
1	Sylvite	0.	0.	0.	0.	0.	0.	52.	48.	0.	0.	0.	0.0
16	Fe-rich	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	99.	0.9
1	Calcite	0.	0.	0.	0.	0.	0.	0.	100.	0.	0.	0.	0.1
19	Mixed Carbonate	0.	0.	1.	1.	0.	8.	0.	0.	12.	1.	77.	0.7
1	Ti-rich	0.	0.	0.	0.	0.	0.	0.	0.	0.	62.	38.	0.0
1	Trace-comp	0.	0.	7.	9.	0.	24.	0.	0.	0.	0.	23.	0.0
17	Quartz-Sulfate	0.	0.	5.	63.	0.	26.	0.	2.	0.	1.	1.	0.6
14	Quartz-Pyrite	0.	0.	1.	49.	0.	26.	0.	2.	0.	0.	22.	1.0
31	Sil-sulf	0.	0.	22.	44.	0.	26.	0.	6.	0.	0.	1.	0.9
10	Silicate-Pyrite	0.	0.	14.	29.	0.	23.	0.	10.	0.	0.	25.	0.8
8	Alumina-rich	0.	0.	89.	2.	0.	5.	0.	0.	4.	0.	0.	0.2
87	Misc. Mixed	0.	0.	9.	20.	0.	21.	4.	6.	4.	0.	32.	6.3
1199	GRAND TOTALS	0.	0.	11.	46.	0.	19.	0.	3.	1.	0.	18.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Quartz	19.8	10.	36.	35.	17.	2.	1.	0.
Illite	7.4	23.	46.	20.	8.	2.	1.	0.
Misc. Silicates	28.7	30.	40.	14.	10.	3.	2.	0.
Pyrite	13.8	13.	7.	27.	39.	8.	6.	0.
Misc. sulf.	10.7	38.	49.	6.	3.	2.	1.	0.
MINOR MINERALS	19.6	27.	25.	13.	18.	11.	7.	0.
GRAND TOTALS	100.0	24.	33.	19.	16.	5.	3.	0.

TABLE 4-8. - PSIT Illinois #6 SOAP coal in carnauba wax

SAMPLE # 485 PSI ILLINOIS #6 SOAP product IN CARNOUBA WAX

RUN 1 DATE 2-MAY-91 SUMMARY 102 TOTAL 485

AVERAGE SPECIES COMPOSITION

#	MINERAL SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Weight %
66	Quartz	0.	0.	0.	99.	0.	0.	0.	0.	0.	0.	0.	10.9
1	Kaolinite	0.	0.	46.	47.	0.	0.	0.	5.	0.	0.	2.	0.1
8	Illite	0.	0.	28.	53.	0.	5.	0.	8.	0.	1.	3.	1.1
61	Misc. Silicates	0.	1.	13.	65.	0.	10.	0.	4.	1.	1.	4.	18.5
10	Elem. Sulfur	0.	0.	0.	2.	0.	89.	0.	1.	0.	1.	0.	1.3
25	Pyrite	0.	0.	0.	0.	0.	64.	0.	0.	0.	0.	36.	5.9
11	Ferrous Sulfate	0.	0.	0.	0.	0.	49.	0.	0.	0.	0.	51.	2.4
6	Jarosite	0.	0.	1.	3.	0.	40.	0.	7.	1.	0.	47.	0.7
19	Gypsum	0.	0.	0.	0.	0.	46.	0.	0.	54.	0.	0.	1.5
1	Chalcopyrite	0.	0.	0.	0.	0.	62.	0.	0.	0.	0.	29.	0.1
81	Misc. sulf.	1.	0.	0.	6.	0.	55.	0.	2.	5.	1.	23.	14.3
5	Fe-rich	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	99.	4.5
4	Calcite	0.	0.	0.	0.	0.	2.	0.	0.	98.	0.	0.	1.7
1	Magnesite	0.	96.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.0
26	Mixed Carbonate	0.	0.	0.	1.	0.	13.	0.	0.	49.	0.	35.	5.3
2	Ti oxide	0.	0.	0.	0.	0.	0.	0.	0.	0.	100.	0.	0.1
1	Ti-rich	0.	0.	0.	7.	0.	14.	0.	0.	0.	61.	0.	0.3
2	Trace-rich	0.	0.	0.	5.	0.	2.	0.	0.	0.	0.	24.	0.8
40	Quartz-Sulfate	0.	0.	1.	45.	0.	44.	1.	2.	0.	2.	1.	5.2
12	Quartz-Pyrite	0.	0.	4.	34.	0.	32.	0.	3.	0.	0.	22.	0.9
32	Sil-sulf	0.	0.	17.	35.	0.	34.	0.	7.	1.	1.	3.	8.2
10	Silicate-Pyrite	0.	0.	16.	37.	0.	27.	0.	1.	1.	0.	16.	3.1
15	Alumina-rich	0.	0.	97.	1.	0.	1.	0.	0.	0.	0.	1.	5.9
41	Misc. Mixed	1.	0.	12.	21.	1.	21.	2.	5.	13.	2.	20.	7.3
480	GRAND TOTALS	0.	0.	11.	33.	0.	25.	0.	2.	7.	1.	17.	100.0

WEIGHT DISTRIBUTION

Size Ranges (Microns)

MINERAL SPECIES	WT. %	0.0	2.5	5.0	10.	20.	40.	80.
		2.5	5.0	10.0	20.	40.	80.	500.
Quartz	10.9	24.	44.	24.	7.	0.	0.	0.
Misc. Silicates	18.5	31.	53.	8.	3.	2.	3.	0.
Misc. sulf.	14.3	43.	29.	16.	11.	0.	0.	0.
Sil-sulf	8.2	11.	72.	14.	3.	0.	0.	0.
Misc. Mixed	7.3	28.	24.	16.	5.	7.	20.	0.
MINOR MINERALS	40.9	46.	29.	17.	8.	1.	0.	0.
GRAND TOTALS	100.0	36.	38.	16.	7.	1.	2.	0.

TABLE 4-9. - Sulfur forms in Gravimelt coals from XANES analysis
 (% of total sulfur in different forms)

	Pittsburgh #8 2.19 wt% S	Gravimelt Pittsburgh #8 0.43 wt% S	Gravimelt Kentucky #9 0.70 wt% S
Pyrite	52	0	0
Elem. sulfur	0	28	37
Org. sulfide	13	0	0
Thiophene	35	19	16
Sulfonate	0	16	14
Sulfate	0	37	33

TABLE 4-10. - PSIT Powder Nepheline on filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 483 PSI POWDER NEPHELINE on filter

NUMBER 483 DISK 51 FILE 125 - 128 PARTICLES
 RUN 1 DATE 17-JUN-91 SUMMARY 128 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.18194E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
14	Al - -	0.	0.	95.	2.	0.	0.	1.	1.	0.	0.	2.	0.	0.	0.	0.	1.1
3	Ca - -	0.	0.	0.	3.	0.	0.	0.	0.	97.	0.	0.	0.	0.	0.	0.	0.6
9	Al Si -	0.	0.	59.	37.	0.	0.	1.	2.	0.	0.	0.	0.	0.	0.	0.	1.0
232	Si Al K	8.	0.	30.	38.	0.	0.	1.	19.	1.	0.	1.	0.	1.	0.	0.	19.7
20	Si K Al	6.	0.	25.	36.	0.	0.	0.	30.	0.	0.	2.	0.	0.	0.	0.	1.7
36	K Si Al	3.	0.	23.	29.	0.	0.	0.	39.	1.	0.	4.	0.	0.	0.	0.	1.9
84	Al Si K	0.	0.	46.	31.	2.	0.	6.	13.	0.	0.	1.	0.	0.	0.	0.	7.4
451	Si Al Na	22.	0.	28.	36.	0.	0.	0.	10.	3.	0.	0.	0.	0.	0.	0.	37.0
80	Na Si Al	35.	0.	23.	30.	0.	0.	2.	6.	4.	0.	0.	0.	0.	0.	0.	6.2
101	Si Na Al	29.	0.	24.	35.	0.	0.	0.	9.	2.	0.	0.	0.	0.	0.	0.	9.2
15	Al Si Na	13.	0.	46.	28.	2.	0.	3.	6.	1.	0.	0.	0.	0.	0.	0.	1.0
4	Ca Si Al	0.	0.	14.	18.	0.	3.	0.	0.	65.	0.	0.	0.	0.	0.	0.	0.6
62	Si Al Ca	4.	0.	32.	45.	0.	0.	1.	1.	16.	0.	0.	0.	1.	0.	0.	6.2
21	Al Si Cl	0.	0.	49.	33.	1.	0.	10.	5.	1.	0.	0.	0.	1.	0.	0.	1.3
64	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.7
1199	TOTALS -	15.	0.	31.	35.	0.	0.	1.	12.	4.	0.	1.	0.	0.	0.	0.	99.8

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si Al K	19.7	21.	25.	13.	25.	12.	4.	0.
Al Si K	7.4	45.	29.	18.	6.	2.	0.	0.
Si Al Na	37.0	14.	39.	26.	12.	6.	2.	0.
Na Si Al	6.2	59.	27.	9.	3.	2.	0.	0.
Si Na Al	9.2	37.	42.	16.	4.	0.	0.	0.
Si Al Ca	6.2	30.	28.	14.	23.	2.	2.	0.
OTHERS -	14.1	20.	18.	12.	32.	15.	2.	0.
TOTALS -	99.8	25.	31.	18.	16.	7.	2.	0.

TABLE 4-11. - PSIT Powder Montmorillonite on filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 482 PSI POWDER MONTMORILLONITE on filter

NUMBER 482 DISK 51 FILE 121 - 124 PARTICLES
 RUN 1 DATE 15-JUN-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 12.00 >>500U 0

TOTAL Volume FACTOR: 0.14073E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
42	Si - -	0.	0.	8.	79.	0.	0.	1.	7.	2.	1.	1.	1.	0.	0.	0.	3.6
279	Si Al -	0.	1.	14.	78.	0.	0.	0.	2.	3.	0.	1.	0.	0.	0.	0.	24.2
18	Si K -	0.	0.	1.	83.	0.	0.	0.	16.	0.	0.	0.	0.	0.	0.	0.	1.7
140	Si Al Ca	0.	0.	14.	77.	0.	0.	0.	1.	7.	0.	1.	0.	0.	0.	0.	12.3
14	Si Ca Al	0.	0.	10.	75.	0.	0.	0.	0.	11.	0.	3.	0.	0.	0.	0.	0.8
232	Si K Al	0.	0.	11.	71.	0.	0.	1.	14.	1.	0.	1.	0.	0.	0.	0.	16.9
396	Si Al K	0.	0.	14.	73.	0.	0.	0.	10.	1.	0.	1.	0.	0.	0.	0.	35.9
74	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.3
1195	TOTALS -	0.	1.	13.	73.	0.	0.	1.	7.	3.	0.	1.	0.	0.	0.	0.	100.0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si Al -	24.2	2.	11.	33.	49.	3.	0.	0.
Si Al Ca	12.3	1.	6.	9.	62.	22.	0.	0.
Si K Al	16.9	20.	49.	29.	2.	0.	0.	0.
Si Al K	35.9	18.	47.	26.	10.	0.	0.	0.
OTHERS -	10.7	30.	28.	14.	18.	9.	0.	0.
TOTALS -	100.0	14.	32.	25.	25.	4.	0.	0.

TABLE 4-12. - PSIT/Arizona Beulah ash on filter 22Im1A. run #2

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 284 PSI/ARIZONA Beulah ash ON FILTER 22Im1A, RUN#2
 NUMBER 284 DISK 43 FILE 104 - 106 PARTICLES
 RUN 1 DATE 26-JAN-90 SUMMARY 106 TOTAL 924
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>5000 0

TOTAL Volume FACTOR: 0.15371E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
27	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	2.	0.	96.	0.	0.	0.	0.	3.5
97	Ca - -	0.	2.	3.	4.	0.	1.	0.	0.	86.	0.	3.	0.	0.	0.	0.	10.7
64	Si - -	0.	0.	0.	98.	0.	0.	0.	1.	0.	0.	1.	0.	0.	0.	0.	7.8
3	Ti - -	0.	0.	0.	0.	0.	0.	0.	0.	1.	99.	0.	0.	0.	0.	0.	0.7
23	Si Al -	0.	0.	24.	71.	0.	0.	0.	3.	1.	0.	1.	0.	0.	0.	0.	2.3
10	Si Ca -	0.	0.	0.	77.	0.	0.	0.	0.	23.	0.	0.	0.	0.	0.	0.	1.1
19	Ca S -	0.	0.	0.	1.	0.	18.	0.	0.	81.	0.	0.	0.	0.	0.	0.	1.9
1	Fe Si -	0.	0.	0.	10.	0.	0.	0.	0.	0.	0.	90.	0.	0.	0.	0.	0.6
169	Ca Si Al	0.	1.	17.	24.	0.	0.	0.	0.	54.	1.	3.	0.	0.	0.	0.	14.2
26	Si Ca Al	2.	0.	19.	43.	0.	2.	0.	1.	31.	0.	2.	0.	0.	0.	0.	3.4
33	Ca Al Si	0.	2.	17.	14.	0.	1.	0.	0.	63.	0.	4.	0.	0.	0.	0.	5.1
48	Si Al Ca	0.	0.	31.	44.	0.	1.	0.	1.	18.	1.	4.	0.	0.	0.	0.	5.4
3	Al Si Ca	0.	0.	48.	40.	0.	0.	0.	0.	13.	0.	0.	0.	0.	0.	0.	0.6
5	Fe Si Al	0.	0.	14.	29.	0.	0.	0.	3.	0.	0.	54.	0.	0.	0.	0.	0.6
44	Si Al Fe	0.	0.	26.	52.	0.	0.	0.	7.	3.	0.	11.	0.	0.	0.	0.	4.4
14	Si Fe Al	0.	0.	17.	47.	0.	0.	0.	7.	1.	0.	27.	0.	0.	0.	0.	1.9
30	Si Al Na	25.	0.	30.	38.	0.	0.	0.	0.	6.	1.	0.	0.	0.	0.	0.	3.0
13	Si Na Al	27.	0.	20.	48.	0.	0.	0.	1.	3.	0.	1.	0.	0.	0.	0.	1.6
112	Si Al K	0.	0.	29.	56.	0.	0.	0.	9.	1.	0.	4.	0.	0.	0.	0.	14.2
11	Ca Si Mg	0.	12.	6.	17.	0.	2.	0.	0.	59.	0.	4.	0.	0.	0.	0.	0.7
15	Ca Mg Si	0.	14.	6.	9.	0.	0.	0.	0.	68.	0.	3.	0.	0.	0.	0.	1.8
14	Ca Fe Si	0.	0.	5.	14.	0.	0.	0.	0.	57.	1.	22.	0.	0.	0.	0.	1.5
13	Ca Si Fe	0.	0.	5.	22.	0.	0.	0.	0.	61.	1.	11.	0.	0.	0.	0.	1.7
2	Si Fe Ca	0.	0.	15.	35.	0.	5.	0.	5.	18.	0.	22.	0.	0.	0.	0.	0.5
4	Fe Ca Si	0.	0.	2.	17.	0.	0.	0.	0.	30.	1.	51.	0.	0.	0.	0.	0.8
2	Fe Si Ca	0.	0.	7.	11.	0.	0.	0.	0.	8.	0.	73.	0.	0.	0.	0.	0.5
6	Ca Si Ti	0.	0.	7.	19.	0.	0.	0.	0.	58.	15.	0.	0.	0.	0.	0.	0.5
1	Ti Si Ca	0.	0.	4.	24.	0.	0.	0.	2.	14.	56.	0.	0.	0.	0.	0.	0.5
18	Ca S Si	0.	0.	4.	11.	0.	20.	0.	0.	62.	0.	2.	0.	0.	0.	0.	1.6
6	Ca S Mg	0.	11.	3.	3.	0.	18.	0.	0.	64.	0.	1.	0.	0.	0.	0.	0.8
1	Ti Ca S	0.	0.	0.	7.	0.	22.	0.	0.	29.	42.	0.	0.	0.	0.	0.	0.5

TABLE 4-12. - PSIT/Arizona Beulah ash on filter 22Im1A, run #2 (Cont.)

4	Si Al Ti	0.	0.	19.	57.	0.	0.	0.	6.	4.	9.	5.	0.	0.	0.	0.	0.7
86	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.1

924	TOTALS -	1.	1.	15.	35.	0.	2.	0.	2.	33.	2.	9.	0.	0.	0.	0.	100.0

SAMPLE # 284 PS1/ARIZONA Beulah ash ON FILTER 22Im1A, RUN#2
 NUMBER 284 DISK 43 FILE 104 - 106 PARTICLES
 RUN 1 DATE 26-JAN-90 SUMMARY 106 TOTAL 924
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.2-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	10.7	0.	1.	18.	53.	18.	9.	0.
Si - -	7.8	0.	5.	33.	47.	10.	4.	0.
Ca Si Al	14.2	2.	15.	34.	36.	12.	2.	0.
Ca Al Si	5.1	0.	7.	8.	76.	6.	3.	0.
Si Al Ca	5.4	0.	16.	26.	48.	10.	0.	0.
Si Al K	14.2	0.	4.	18.	64.	15.	0.	0.
Si Al Fe	4.4	0.	7.	37.	41.	13.	2.	0.
OTHERS -	38.2	0.	6.	17.	55.	19.	3.	0.
TOTALS -	100.0	0.	7.	22.	53.	15.	3.	0.

**TABLE 4-13. - PSIT/Arizona Beulah Lignite ash on filter.
Impactor #3, 22IM3**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 286 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #3, 22IM3.
 NUMBER 3 DISK 32 FILE 109 - 112 PARTICLES
 RUN 1 DATE 18-JUN-89 SUMMARY 112 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.33900E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
24	Si - -	0.	0.	2.	93.	0.	0.	0.	2.	1.	0.	1.	0.	0.	0.	0.	3.2
11	Ca - -	0.	0.	2.	2.	0.	1.	0.	0.	92.	0.	2.	0.	0.	0.	0.	1.1
5	Si Ca -	0.	0.	1.	76.	0.	1.	0.	4.	13.	3.	1.	1.	0.	0.	0.	0.5
19	Si Al -	1.	0.	32.	58.	0.	1.	0.	4.	2.	0.	3.	0.	0.	0.	0.	2.9
7	Ca S -	1.	0.	0.	1.	0.	29.	0.	0.	67.	0.	2.	0.	0.	0.	0.	0.9
108	Si Al Ca	5.	0.	27.	39.	0.	2.	0.	3.	16.	1.	5.	0.	0.	0.	0.	7.9
304	Ca Si Al	4.	3.	17.	23.	0.	4.	0.	0.	44.	1.	3.	0.	0.	0.	0.	22.4
49	Si Ca Al	9.	0.	20.	36.	0.	3.	0.	1.	25.	1.	4.	0.	0.	0.	0.	3.5
49	Ca Al Si	3.	3.	19.	16.	0.	4.	0.	0.	50.	1.	4.	0.	0.	0.	0.	3.9
95	Si Al Na	22.	0.	29.	37.	0.	1.	0.	1.	9.	0.	2.	0.	0.	0.	0.	8.8
22	Na Si Al	34.	0.	24.	30.	0.	1.	1.	1.	7.	1.	1.	0.	0.	0.	0.	1.6
49	Si Na Al	28.	0.	25.	35.	0.	1.	0.	0.	8.	1.	2.	0.	0.	0.	0.	4.0
11	Si Ca Na	15.	0.	5.	53.	0.	3.	0.	0.	18.	0.	5.	0.	0.	0.	0.	0.6
6	Ca Si Na	17.	1.	13.	28.	0.	4.	1.	0.	32.	1.	4.	0.	0.	0.	0.	0.8
10	Si Na Ca	26.	0.	10.	44.	0.	3.	1.	0.	14.	0.	2.	0.	0.	0.	0.	1.2
25	Ca Si S	1.	3.	10.	17.	0.	12.	0.	0.	53.	0.	4.	0.	0.	0.	0.	1.7
30	Ca S Si	2.	3.	9.	12.	0.	23.	1.	1.	45.	1.	2.	0.	1.	0.	0.	2.3
3	S Ca Si	0.	0.	12.	12.	5.	39.	0.	1.	31.	0.	0.	0.	0.	0.	0.	0.8
7	Si Ca S	1.	1.	7.	62.	0.	9.	0.	0.	16.	0.	4.	0.	0.	0.	0.	0.5
20	Ca S Al	2.	5.	11.	7.	0.	22.	0.	0.	50.	1.	2.	0.	0.	0.	0.	1.8
13	Ca Al S	0.	6.	15.	8.	0.	10.	0.	0.	58.	0.	3.	0.	0.	0.	0.	0.7
44	Si Al K	1.	0.	29.	54.	0.	0.	0.	8.	2.	1.	5.	0.	0.	0.	0.	6.9
5	Fe Si Al	4.	0.	20.	29.	0.	2.	0.	5.	5.	1.	35.	0.	0.	0.	0.	0.5
62	Si Al Fe	1.	0.	28.	49.	0.	1.	0.	6.	4.	1.	10.	0.	0.	0.	0.	5.2
5	Si Fe Al	2.	0.	17.	37.	0.	2.	1.	7.	8.	2.	24.	0.	0.	0.	0.	1.2
11	Ca Mg Al	1.	18.	11.	5.	0.	4.	0.	0.	54.	2.	5.	0.	0.	0.	0.	1.1
6	Ca Si Fe	2.	1.	12.	25.	0.	5.	0.	0.	38.	1.	14.	0.	0.	0.	0.	0.5
5	Ca Fe Si	0.	3.	8.	12.	0.	2.	0.	0.	56.	0.	20.	0.	0.	0.	0.	0.9
3	Si Ca Fe	0.	0.	10.	41.	0.	6.	0.	1.	29.	1.	12.	0.	0.	0.	0.	0.7
11	Ca Mg Si	4.	17.	7.	13.	0.	3.	1.	0.	51.	0.	3.	0.	0.	0.	0.	1.1
5	Ca S Fe	0.	5.	6.	9.	0.	16.	0.	0.	54.	1.	9.	0.	0.	0.	0.	0.5

TABLE 4-13. - PSIT/Arizona Beulah Lignite ash on filter, Impactor #3, 22IM3 (Cont.)

16	Ca S Mg	0.	12.	8.	3.	0.	17.	0.	0.	57.	0.	2.	0.	0.	0.	0.	1.1
8	Ca Mg S	0.	16.	7.	7.	0.	11.	0.	0.	51.	0.	7.	0.	0.	0.	0.	0.6
1	Ca Zn S	0.	0.	11.	11.	0.	13.	12.	8.	33.	0.	0.	0.	14.	0.	0.	0.7
5	Si Al Ti	0.	0.	28.	39.	0.	5.	0.	0.	10.	16.	0.	0.	0.	0.	0.	0.5
4	Ca Mg Fe	0.	18.	7.	0.	0.	0.	0.	0.	66.	0.	9.	0.	0.	0.	0.	0.5
105	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.5
1164	TOTALS -	7.	2.	19.	32.	0.	5.	0.	2.	27.	1.	5.	0.	0.	0.	0.	100.0

SAMPLE # 286 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #3, 22IM3.
 NUMBER 3 DISK 32 FILE 109 - 112 PARTICLES
 RUN 1 DATE 18-JUN-89 SUMMARY 112 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-1.0	1.0-2.0	2.0- 5.	5.- 7.	7.- 10.	10.- 20.	20.-500.
Si Al Ca	7.9	0.	6.	31.	46.	10.	6.	0.
Ca Si Al	22.4	0.	9.	46.	34.	7.	3.	0.
Si Al Na	8.8	0.	9.	44.	37.	3.	2.	6.
Si Na Al	4.0	1.	11.	67.	16.	4.	1.	0.
Si Al K	6.9	0.	1.	46.	49.	1.	3.	0.
Si Al Fe	5.2	0.	7.	72.	15.	4.	2.	0.
OTHERS -	44.9	0.	7.	38.	39.	5.	5.	6.
TOTALS -	100.0	0.	7.	43.	37.	5.	4.	3.

TABLE 4-14. - PSIT/Arizona Beulah Lignite ash on filter, Impactor #5, 22IM5

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 288 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #5, 22IM5.

NUMBER 4 DISK 34 FILE 113 - 116 PARTICLES

RUN 1 DATE 15-JUN-89 SUMMARY 116 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.19807E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
546	Ca Si Al	5.	3.	17.	22.	0.	7.	0.	0.	40.	2.	4.	0.	0.	0.	0.	39.3
77	Si Ca Al	10.	1.	21.	31.	0.	5.	0.	0.	25.	2.	3.	0.	0.	0.	0.	5.8
30	Ca Al Si	3.	2.	22.	20.	0.	6.	0.	0.	41.	1.	3.	0.	0.	0.	0.	2.9
63	Si Al Ca	9.	1.	28.	35.	0.	3.	0.	1.	20.	1.	3.	0.	0.	0.	0.	5.5
74	Ca Si S	6.	3.	13.	19.	0.	15.	0.	0.	39.	1.	4.	0.	0.	0.	0.	5.5
52	Ca S Si	5.	3.	10.	15.	0.	22.	0.	1.	39.	1.	4.	0.	0.	0.	0.	4.3
36	Ca Si Na	18.	2.	15.	22.	0.	9.	0.	0.	31.	1.	2.	0.	0.	0.	0.	3.1
5	Si Na Ca	27.	0.	10.	35.	0.	4.	0.	0.	19.	4.	2.	0.	0.	0.	0.	0.5
11	Si Ca Na	19.	2.	11.	32.	0.	7.	0.	1.	25.	1.	3.	0.	0.	0.	0.	1.4
30	Si Na Al	29.	0.	25.	33.	0.	1.	0.	0.	9.	0.	2.	0.	0.	0.	0.	3.4
54	Si Al Na	22.	0.	27.	32.	0.	3.	0.	0.	12.	1.	2.	0.	1.	0.	0.	6.2
28	Na Si Al	33.	0.	24.	29.	0.	1.	0.	0.	10.	1.	2.	0.	0.	0.	0.	2.9
4	Na Ca S	30.	3.	6.	13.	0.	19.	2.	0.	24.	7.	2.	0.	0.	0.	0.	0.5
14	Ca S Na	17.	6.	10.	10.	0.	22.	0.	0.	31.	1.	3.	0.	0.	0.	0.	1.5
10	Ca Na S	22.	3.	12.	12.	0.	18.	0.	0.	28.	2.	3.	0.	1.	0.	0.	0.9
10	Ca S Mg	0.	13.	7.	6.	0.	20.	0.	0.	46.	2.	6.	0.	0.	0.	0.	0.9
17	Si Al Fe	0.	0.	29.	48.	0.	3.	0.	4.	3.	2.	11.	0.	0.	0.	0.	1.9
16	Ca S Al	1.	3.	14.	10.	0.	25.	0.	0.	43.	0.	4.	0.	0.	0.	0.	1.5
7	Ca Al S	3.	1.	18.	13.	0.	16.	0.	0.	41.	3.	5.	0.	0.	0.	0.	0.8
7	Ca Mg Si	0.	22.	9.	12.	0.	5.	0.	0.	46.	1.	5.	0.	0.	0.	0.	0.5
7	Ca Si Mg	2.	14.	10.	18.	0.	6.	0.	0.	46.	1.	4.	0.	0.	0.	0.	1.1
2	Si Ca Ti	0.	5.	7.	45.	0.	1.	0.	0.	29.	8.	6.	0.	0.	0.	0.	0.6
93	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.6
1193	TOTALS -	9.	3.	18.	24.	0.	8.	0.	1.	32.	2.	4.	0.	0.	0.	0.	100.0

TABLE 4-14. - PSIT/Arizona Beulah Lignite ash on filter, Impactor #5, 22IM5 (Cont.)

SAMPLE # 288 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #5, 22IM5.
 NUMBER 4 DISK 34 FILE 113 - 116 PARTICLES
 RUN 1 DATE 15-JUN-89 SUMMARY 116 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-1.5	1.5-3.0	3.0- 5.	5.- 6.	6.- 8.	8.- 10.	10.-500.
Ca Si Al	39.3	6.	37.	16.	20.	8.	6.	8.
Si Ca Al	5.8	7.	40.	26.	13.	6.	4.	5.
Si Al Ca	5.5	11.	36.	28.	21.	2.	1.	2.
Ca Si S	5.5	3.	31.	25.	24.	7.	6.	5.
Ca S Si	4.3	7.	28.	33.	24.	2.	2.	2.
Si Al Na	6.2	8.	64.	20.	8.	1.	1.	0.
OTHERS -	33.6	9.	62.	16.	9.	2.	1.	1.
TOTALS -	100.0	7.	47.	18.	15.	5.	3.	4.

TABLE 4-15. - PSIT/Arizona Beulah Lignite ash on filter, Impactor #7, 22IM7

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 290 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #7, 22IM7.

NUMBER 2 DISK 34 FILE 109 - 112 PARTICLES
 RUN 1 DATE 14JUN-89 SUMMARY 112 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.34133E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
10	K - -	0.	0.	3.	0.	0.	0.	0.	95.	0.	0.	1.	0.	1.	0.	0.	0.5
3	Ca Fe S	0.	0.	0.	11.	0.	13.	0.	0.	44.	6.	26.	0.	0.	0.	0.	0.7
570	Ca S Si	6.	2.	11.	15.	0.	21.	0.	0.	39.	2.	4.	0.	0.	0.	0.	38.3
120	Ca Si S	5.	3.	13.	19.	0.	16.	0.	0.	39.	2.	3.	0.	0.	0.	0.	9.2
17	Ca S Al	0.	2.	16.	14.	0.	25.	0.	0.	37.	2.	2.	0.	1.	0.	0.	2.1
5	S Ca Na	21.	0.	1.	3.	0.	42.	0.	0.	24.	2.	2.	1.	2.	0.	0.	0.7
73	Ca S Na	17.	2.	10.	13.	0.	22.	0.	0.	32.	1.	3.	0.	0.	0.	0.	10.1
33	Ca Na S	22.	2.	10.	12.	0.	19.	0.	0.	30.	1.	3.	0.	0.	0.	0.	5.1
7	Na Ca S	30.	0.	11.	14.	0.	19.	0.	0.	25.	0.	0.	0.	0.	0.	0.	1.6
133	Ca Si Al	4.	2.	17.	23.	0.	8.	0.	1.	41.	1.	3.	0.	0.	0.	0.	13.3
14	Si Al Ca	11.	1.	23.	33.	0.	5.	0.	1.	19.	3.	3.	1.	0.	0.	0.	1.5
28	Ca Al Si	7.	1.	21.	19.	0.	8.	0.	0.	37.	1.	3.	0.	1.	0.	0.	2.4
18	Si Ca Al	4.	0.	24.	35.	0.	6.	0.	0.	28.	1.	1.	0.	0.	0.	0.	1.5
9	Ca Na Si	20.	2.	15.	17.	0.	13.	0.	0.	30.	1.	2.	0.	0.	0.	0.	1.0
11	Ca Si Na	17.	2.	14.	22.	0.	11.	0.	1.	29.	1.	4.	0.	0.	0.	0.	1.4
2	Na Si Ca	24.	0.	18.	20.	0.	14.	0.	0.	19.	2.	3.	0.	0.	0.	0.	0.9
4	Na Si Al	36.	0.	23.	25.	0.	4.	0.	0.	8.	1.	2.	0.	0.	0.	0.	0.5
14	Si Al Na	23.	0.	28.	33.	0.	1.	0.	0.	11.	1.	2.	0.	0.	0.	0.	0.8
10	Si Na Al	28.	0.	22.	30.	0.	4.	0.	0.	13.	1.	2.	0.	0.	0.	0.	1.5
95	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.9
1176	TOTALS -	9.	2.	13.	17.	0.	17.	0.	1.	35.	2.	4.	0.	0.	0.	0.	100.0

TABLE 4-15. - PSIT/Arizona Beulah Lignite ash on filter, Impactor #7, 22IM7 (Cont.)

SAMPLE # 290 PSI/ARIZONA BEULAH LIGNITE ash ON filter, Imp. #7, 22IM7.

NUMBER 2 DISK 34 FILE 109 - 112 PARTICLES

RUN 1 DATE 14JUN-89 SUMMARY 112 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Ca S Si	38.3	11.	22.	21.	33.	13.	0.	0.
Ca Si S	9.2	24.	12.	34.	25.	6.	0.	0.
Ca S Na	10.1	23.	42.	23.	11.	1.	0.	0.
Ca Na S	5.1	18.	57.	22.	3.	0.	0.	0.
Ca Si Al	13.3	58.	26.	8.	9.	0.	0.	0.
OTHERS -	23.9	73.	18.	5.	1.	2.	0.	0.
TOTALS -	100.0	35.	24.	17.	17.	6.	0.	0.

TABLE 4-16. - PSIT Beulah ash 7% oxygen on filter paper

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI beulah ash 7% oxygen on filter paper

NUMBER 1 DISK 19 FILE 110 - 113 PARTICLES
RUN 1 DATE 2-AUG-88 SUMMARY 113 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.50051E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
177	Ca - -	0.	4.	2.	4.	0.	2.	0.	0.	83.	2.	3.	0.	0.	0.	0.	20.2
16	Fe - -	0.	0.	1.	0.	0.	0.	0.	0.	3.	2.	93.	0.	0.	0.	0.	1.9
25	Si - -	2.	0.	0.	93.	0.	0.	0.	0.	2.	1.	0.	0.	1.	0.	0.	2.1
16	Ca Mg -	0.	13.	0.	2.	0.	2.	0.	0.	79.	2.	2.	0.	0.	0.	0.	1.5
4	Fe Ca -	0.	0.	1.	2.	0.	1.	0.	0.	29.	3.	63.	0.	0.	0.	0.	0.5
3	Al Si -	4.	0.	52.	43.	0.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.5
10	Si Na -	15.	0.	1.	82.	0.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	1.2
3	Si Ca -	0.	0.	0.	82.	0.	0.	0.	1.	16.	0.	0.	0.	1.	0.	0.	0.6
11	Ca Si -	0.	3.	2.	15.	0.	1.	0.	0.	76.	1.	2.	0.	1.	0.	0.	1.9
4	Ca Ti -	0.	3.	1.	4.	0.	0.	0.	0.	66.	25.	1.	0.	0.	0.	0.	0.5
11	Ca Si Fe	0.	1.	3.	15.	0.	0.	0.	0.	67.	4.	9.	0.	1.	0.	0.	1.0
6	Ca Fe Si	0.	5.	6.	10.	0.	0.	0.	0.	64.	2.	12.	0.	0.	0.	0.	0.6
18	Ca Si Na	16.	3.	11.	23.	0.	1.	0.	0.	41.	2.	3.	0.	0.	0.	0.	1.4
14	Si Na Ca	21.	0.	3.	62.	0.	0.	0.	1.	11.	2.	0.	0.	0.	0.	0.	2.1
9	Si Ca Na	15.	1.	6.	54.	0.	1.	0.	0.	19.	1.	1.	0.	1.	0.	0.	0.6
7	Ca Si Ti	0.	3.	2.	15.	0.	1.	0.	0.	65.	9.	3.	0.	1.	0.	0.	0.5
27	Ca Mg Si	1.	15.	5.	9.	0.	2.	0.	0.	64.	0.	2.	0.	1.	0.	0.	1.8
25	Ca Si Mg	1.	9.	6.	15.	0.	1.	0.	0.	63.	2.	2.	0.	0.	0.	0.	1.6
79	Ca Al Si	3.	5.	20.	16.	0.	1.	0.	0.	50.	2.	3.	0.	0.	0.	0.	6.0
200	Ca Si Al	3.	3.	15.	21.	0.	1.	0.	0.	52.	2.	2.	0.	0.	0.	0.	16.9
21	Si Al Ca	9.	1.	28.	38.	0.	0.	0.	1.	19.	2.	1.	0.	0.	0.	0.	2.2
19	Si Ca Al	13.	1.	21.	33.	0.	1.	0.	0.	27.	1.	2.	0.	1.	0.	0.	1.2
13	Al Si Ca	7.	1.	37.	31.	0.	0.	0.	0.	19.	1.	1.	0.	2.	0.	0.	2.1
5	Al Ca Si	18.	1.	28.	25.	0.	0.	2.	0.	26.	0.	0.	0.	0.	0.	0.	0.5
34	Al Si Na	22.	0.	37.	33.	0.	1.	0.	0.	6.	1.	1.	0.	1.	0.	0.	3.3
58	Si Al Na	21.	0.	30.	35.	0.	1.	0.	1.	10.	0.	1.	0.	1.	0.	0.	4.9
25	Si Na Al	27.	1.	23.	38.	0.	0.	0.	1.	8.	0.	1.	1.	0.	0.	0.	1.9
9	Al Na Si	30.	0.	31.	26.	0.	1.	1.	0.	7.	1.	1.	0.	0.	0.	0.	0.8
17	Na Al Si	34.	1.	28.	25.	0.	1.	0.	1.	6.	1.	2.	0.	0.	0.	0.	1.2
43	Na Si Al	36.	0.	23.	28.	0.	1.	1.	1.	7.	1.	1.	0.	1.	0.	0.	4.4
2	Ca Ti Fe	0.	0.	2.	2.	0.	2.	0.	0.	74.	13.	7.	0.	0.	0.	0.	0.5

TABLE 4-16. - PSIT Beulah ash 7% oxygen on filter paper (Cont.)

1	Ca Si Zn	0.	0.	6.	24.	0.	0.	13.	0.	31.	0.	5.	0.	21.	0.	0.	0.6
6	Ca S Mg	1.	13.	2.	2.	0.	20.	1.	2.	51.	0.	2.	3.	3.	0.	0.	0.5
7	Ca Mg Fe	1.	14.	2.	3.	0.	1.	0.	0.	69.	2.	9.	0.	0.	0.	0.	0.6
4	Ca Ti S	0.	6.	5.	4.	0.	12.	0.	0.	40.	29.	2.	0.	2.	0.	0.	0.7
12	Ca Mg Al	0.	15.	10.	7.	0.	1.	0.	0.	62.	4.	1.	0.	1.	0.	0.	0.7
12	Ca Al Mg	0.	10.	15.	5.	0.	1.	0.	0.	67.	1.	2.	0.	0.	0.	0.	0.7
1	Si Al Zn	0.	0.	21.	24.	5.	0.	10.	0.	15.	0.	0.	10.	15.	0.	0.	0.5
5	Ca Ti Al	0.	4.	14.	11.	0.	1.	0.	0.	50.	17.	3.	0.	0.	0.	0.	0.6
98	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.3
1057	TOTALS -	7.	3.	12.	21.	0.	2.	0.	0.	46.	3.	5.	0.	1.	0.	0.	100.0

SAMPLE PSI beulah ash 7% oxygen on filter paper

NUMBER 1 DISK 19 FILE 110 - 113 PARTICLES
 RUN 1 DATE 2-AUG-88 SUMMARY 113 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.1-0.5	0.5-2.0	2.0- 5.	5.- 10.	10.- 20.	20.- 50.	50.-500.
Ca - -	20.2	0.	2.	7.	62.	13.	8.	7.
Ca Al Si	6.0	0.	34.	12.	44.	8.	2.	0.
Ca Si Al	16.9	0.	24.	8.	54.	9.	6.	0.
Si Al Na	4.9	0.	19.	9.	54.	10.	7.	0.
Na Si Al	4.4	0.	20.	16.	60.	2.	2.	0.
OTHERS -	47.6	0.	16.	7.	52.	11.	10.	4.
TOTALS -	100.0	0.	16.	8.	54.	10.	8.	3.

TABLE 4-17. - PSIT Beulah 21% oxygen ash on filter paper

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI Beulah 21% oxygen ash on filter paper

NUMBER 1 DISK 17 FILE 124 - 127 PARTICLES
 RUN 2 DATE 9/23/88 SUMMARY 127 TOTAL 1199
 BLOCKS 0 TIME 1930 OFF-PT. 43.00 >>5000 0

TOTAL Volume FACTOR: 0.45639E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
24	Si - -	7.	0.	1.	87.	0.	1.	0.	0.	4.	0.	0.	0.	0.	0.	0.	1.6
119	Ca - -	0.	5.	3.	4.	0.	3.	0.	0.	80.	1.	2.	0.	0.	0.	0.	9.0
22	Fe - -	0.	0.	0.	0.	0.	0.	0.	0.	2.	2.	96.	0.	0.	0.	0.	1.0
14	Si Na -	17.	0.	1.	78.	0.	0.	0.	0.	3.	0.	0.	0.	0.	0.	0.	1.1
9	Ca Mg -	0.	13.	2.	4.	0.	4.	0.	0.	72.	1.	3.	0.	0.	0.	0.	1.4
20	Si Na Al	29.	2.	27.	31.	0.	0.	0.	0.	8.	1.	2.	0.	0.	0.	0.	1.6
101	Si Al Na	24.	1.	29.	33.	0.	0.	0.	0.	11.	0.	1.	0.	0.	0.	0.	6.7
60	Al Si Na	23.	1.	34.	30.	0.	0.	0.	0.	11.	0.	1.	0.	0.	0.	0.	3.2
11	Al Na Si	29.	0.	32.	26.	0.	0.	0.	0.	10.	1.	2.	0.	0.	0.	0.	0.6
18	Na Al Si	34.	0.	29.	27.	0.	1.	0.	0.	8.	1.	0.	0.	0.	0.	0.	1.9
36	Na Si Al	31.	2.	24.	27.	0.	2.	0.	0.	13.	0.	1.	0.	0.	0.	0.	4.6
25	Si Ca Al	12.	2.	23.	34.	0.	0.	0.	0.	27.	0.	2.	0.	0.	0.	0.	1.2
329	Ca Si Al	3.	5.	16.	21.	0.	1.	0.	0.	50.	1.	3.	0.	0.	0.	0.	30.6
113	Ca Al Si	3.	5.	21.	18.	0.	1.	0.	0.	47.	2.	2.	0.	0.	0.	0.	9.3
10	Al Si Ca	13.	1.	32.	29.	0.	2.	0.	0.	22.	0.	0.	0.	0.	0.	0.	0.9
27	Si Al Ca	12.	2.	29.	31.	0.	1.	0.	0.	22.	2.	1.	0.	0.	0.	0.	3.8
11	Si Ca Na	14.	2.	7.	52.	0.	0.	0.	0.	23.	2.	0.	0.	0.	0.	0.	0.7
9	Ca Si Na	16.	3.	12.	27.	0.	1.	0.	0.	39.	0.	1.	0.	0.	0.	0.	0.7
13	Si Na Ca	24.	2.	5.	51.	0.	0.	0.	0.	15.	2.	0.	0.	0.	0.	0.	1.8
5	Ca S Al	0.	6.	8.	5.	0.	14.	0.	0.	66.	0.	2.	0.	0.	0.	0.	1.3
6	Ca S Si	0.	4.	3.	9.	0.	18.	0.	0.	63.	0.	2.	0.	0.	0.	0.	0.6
5	Ca Si S	0.	0.	11.	23.	0.	15.	0.	0.	47.	1.	1.	0.	1.	0.	0.	0.6
25	Ca Si Mg	0.	10.	7.	14.	0.	2.	0.	0.	63.	1.	2.	0.	0.	0.	0.	1.8
20	Ca Mg Si	0.	14.	7.	9.	0.	2.	0.	0.	67.	0.	2.	0.	0.	0.	0.	1.2
5	Fe Ca Si	0.	3.	6.	7.	0.	0.	0.	0.	25.	0.	58.	0.	0.	0.	0.	0.5
7	Ca Si Fe	0.	4.	9.	20.	0.	0.	0.	1.	56.	0.	11.	0.	0.	0.	0.	0.7
14	Ca Mg Al	0.	14.	11.	7.	0.	1.	0.	0.	63.	1.	3.	0.	0.	0.	0.	0.9
15	Ca Al Mg	0.	14.	18.	9.	0.	2.	0.	0.	53.	1.	2.	0.	0.	0.	0.	0.8
15	Ca Mg S	0.	16.	7.	5.	0.	11.	0.	0.	59.	1.	2.	0.	0.	0.	0.	1.9
6	Ca S Mg	2.	11.	7.	7.	0.	14.	0.	0.	57.	0.	2.	0.	0.	0.	0.	0.7
3	Ca Ti Si	0.	1.	2.	9.	0.	2.	0.	0.	48.	35.	3.	0.	0.	0.	0.	0.6
1	Si Ca Ti	14.	5.	3.	36.	0.	0.	0.	0.	28.	14.	0.	0.	0.	0.	0.	0.6

TABLE 4-17. - PSIT Beulah 21% oxygen ash on filter paper (Cont.)

95 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE 5.7

 1193 TOTALS - 8. 4. 16. 22. 0. 2. 0. 0. 42. 2. 4. 0. 0. 0. 0. 100.0

SAMPLE PSI Beulah 21% oxygen ash on filter paper
 NUMBER 1 DISK 17 FILE 124 - 127 PARTICLES
 RUN 2 DATE 9/23/88 SUMMARY 127 TOTAL 1199
 BLOCKS 0 TIME 1930 OFF-PT. 48.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.2-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	9.0	9.	3.	68.	17.	3.	0.	0.
Si Al Na	6.7	20.	34.	30.	10.	6.	0.	0.
Na Si Al	4.6	16.	48.	14.	20.	2.	0.	0.
Ca Si Al	30.6	20.	38.	32.	8.	1.	0.	0.
Ca Al Si	9.3	34.	31.	33.	2.	1.	0.	0.
OTHERS -	39.7	19.	34.	28.	15.	4.	0.	0.
TOTALS -	100.0	20.	33.	33.	12.	3.	0.	0.

TABLE 4-18. - Arizona Eagle Butte ash on filter, Impactor #1, 23IM1

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 293 PSI/ARIZONA EAGLE BUTTE ash ON filter, Impactor #1, 23IM1.

NUMBER 2 DISK 32 FILE 105 - 108 PARTICLES

RUN 1 DATE 18-JUN-89 SUMMARY 108 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.34122E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
131	Si - -	1.	0.	1.	96.	0.	0.	0.	1.	2.	0.	0.	0.	0.	0.	0.	8.7
91	Ca - -	0.	3.	6.	3.	0.	3.	0.	0.	78.	0.	5.	0.	0.	0.	0.	8.0
10	Fe - -	0.	0.	0.	1.	0.	0.	0.	0.	4.	0.	95.	0.	0.	0.	0.	1.4
19	Al Si -	1.	0.	52.	45.	0.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.5
26	Si Al -	0.	0.	28.	64.	0.	0.	0.	4.	2.	0.	1.	0.	0.	0.	0.	3.0
35	Si Ca -	2.	0.	0.	74.	0.	0.	0.	0.	22.	0.	1.	0.	0.	0.	0.	2.9
17	Ca Si -	1.	2.	3.	29.	0.	0.	0.	0.	62.	1.	2.	0.	0.	0.	0.	1.7
31	Ca Al -	0.	3.	16.	2.	1.	2.	0.	0.	73.	0.	4.	0.	0.	0.	0.	3.3
6	Ca Fe -	0.	0.	3.	2.	0.	1.	0.	0.	80.	0.	14.	0.	0.	0.	0.	0.6
91	Ca Si Al	1.	2.	14.	24.	0.	3.	0.	1.	51.	1.	4.	0.	0.	0.	0.	6.6
73	Si Al Ca	2.	0.	25.	49.	0.	2.	0.	5.	12.	1.	5.	0.	0.	0.	0.	7.4
35	Si Ca Al	2.	0.	16.	52.	0.	1.	0.	2.	21.	2.	3.	0.	0.	0.	0.	4.4
9	Al Si Ca	6.	0.	47.	33.	0.	0.	0.	3.	9.	3.	0.	0.	0.	0.	0.	1.2
59	Ca Al Si	0.	2.	17.	12.	0.	3.	0.	0.	59.	1.	5.	0.	0.	0.	0.	5.4
23	Ca Si Fe	0.	1.	6.	19.	0.	1.	0.	2.	61.	1.	10.	0.	0.	0.	0.	2.5
11	Ca Fe Si	0.	2.	5.	14.	0.	2.	0.	0.	59.	1.	17.	0.	0.	0.	0.	0.6
12	Ca Si S	0.	1.	7.	18.	0.	9.	0.	0.	59.	0.	4.	0.	0.	0.	0.	1.7
28	Ca S Si	0.	4.	8.	12.	0.	19.	0.	0.	52.	1.	4.	0.	0.	0.	0.	1.5
28	Si Al Na	17.	0.	33.	39.	0.	0.	0.	2.	7.	0.	2.	0.	0.	0.	0.	3.4
5	Si Al Ti	0.	0.	26.	48.	0.	0.	0.	3.	7.	10.	7.	0.	0.	0.	0.	0.7
7	Ca S Cl	0.	3.	4.	2.	0.	27.	10.	0.	52.	1.	1.	0.	0.	0.	0.	0.5
38	Si Al Fe	0.	0.	26.	49.	0.	0.	0.	6.	7.	2.	10.	0.	0.	0.	0.	2.9
7	Si Fe Al	0.	0.	18.	37.	0.	0.	0.	8.	10.	2.	26.	0.	0.	0.	0.	0.7
24	Ca Mg Al	0.	16.	9.	3.	1.	3.	0.	0.	64.	0.	5.	0.	0.	0.	0.	1.4
27	Ca Al Mg	0.	10.	14.	2.	0.	3.	0.	0.	65.	0.	5.	0.	0.	0.	0.	2.5
13	Ca Fe Al	0.	2.	8.	1.	0.	2.	0.	0.	72.	0.	16.	0.	0.	0.	0.	1.0
36	Ca Al Fe	0.	2.	15.	1.	0.	3.	0.	0.	70.	0.	7.	0.	0.	0.	0.	3.6
30	Ca S Al	0.	5.	11.	6.	0.	17.	0.	0.	57.	0.	3.	0.	0.	0.	0.	2.1
40	Ca Al S	0.	5.	15.	3.	0.	9.	0.	0.	63.	1.	5.	0.	0.	0.	0.	2.5
63	Si Al K	0.	0.	25.	58.	0.	0.	0.	9.	3.	0.	4.	0.	0.	0.	0.	8.1

TABLE 4-18. - Arizona Eagle Butte ash on filter, Impactor #1, 23IM1 (Cont.)

12	Ca Mg Fe	0.	13.	6.	1.	0.	2.	0.	0.	69.	0.	8.	0.	0.	0.	0.	0.6
8	Ca Al P	0.	2.	28.	0.	12.	0.	0.	0.	55.	2.	1.	0.	0.	0.	0.	0.5
6	Si Ca Ti	0.	0.	8.	57.	0.	0.	0.	0.	23.	9.	2.	0.	0.	0.	0.	0.5
15	Ca Si Mg	0.	7.	5.	17.	0.	1.	1.	0.	66.	0.	3.	0.	0.	0.	0.	1.4
17	Ca S Fe	0.	5.	6.	3.	0.	16.	0.	0.	56.	1.	12.	0.	0.	0.	0.	1.1
6	Si Ca Na	13.	0.	3.	64.	0.	0.	0.	0.	18.	2.	1.	0.	0.	0.	0.	0.8
96	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.2
<hr/>																	
1186	TOTALS -	1.	2.	14.	33.	0.	3.	0.	2.	37.	1.	6.	0.	0.	0.	0.	100.0

SAMPLE # 293 PSI/ARIZONA EAGLE BUTTE ash ON filter, Impactor #1, 23IM1.
NUMBER 2 DISK 32 FILE 105 - 108 PARTICLES
RUN 1 DATE 18-JUN-89 SUMMARY 108 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	8.7	1.	10.	40.	33.	17.	1.	0.
Ca - -	8.0	2.	18.	38.	35.	7.	0.	0.
Ca Si Al	6.6	7.	13.	42.	34.	4.	0.	0.
Si Al Ca	7.4	3.	14.	51.	28.	3.	1.	0.
Si Ca Al	4.4	1.	8.	34.	52.	5.	0.	0.
Ca Al Si	5.4	7.	30.	19.	43.	1.	0.	0.
Si Al K	8.1	0.	4.	63.	30.	3.	0.	0.
OTHERS -	51.5	4.	16.	39.	34.	6.	0.	0.
TOTALS -	100.0	4.	15.	41.	34.	6.	0.	0.

TABLE 4-19. - Arizona Eagle Butte ash on filter, Impactor #5, 23IM5

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE #297 PSI/ARIZONA EAGLE BUTTE ash ON filter, Imp. #5, 23IM5.

NUMBER 1 DISK 32 FILE 101 - 104 PARTICLES
 RUN 1 DATE 17-JUN-89 SUMMARY 104 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.46489E+04

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
8	Ca - -	0.	5.	9.	5.	1.	6.	0.	0.	67.	2.	6.	0.	0.	0.	0.	0.8
5	Si - -	1.	0.	1.	88.	0.	1.	0.	2.	5.	0.	1.	0.	0.	0.	0.	0.5
12	Ca Al -	0.	1.	34.	2.	2.	3.	0.	0.	53.	2.	4.	0.	0.	0.	0.	0.7
83	Ca S Al	0.	4.	12.	5.	0.	17.	1.	0.	55.	1.	6.	0.	0.	0.	0.	11.3
72	Ca Al S	0.	3.	17.	5.	0.	11.	0.	0.	56.	1.	6.	0.	0.	0.	0.	7.4
9	Si Ca Fe	0.	1.	1.	59.	0.	2.	0.	0.	25.	2.	10.	0.	0.	0.	0.	0.6
9	Ca Si Fe	0.	5.	4.	20.	0.	3.	0.	0.	55.	2.	10.	0.	0.	0.	0.	0.7
12	Si Al Fe	0.	0.	28.	46.	0.	1.	0.	4.	8.	1.	12.	0.	0.	0.	0.	1.1
59	Si Al Ca	3.	0.	30.	38.	0.	2.	0.	1.	20.	1.	3.	0.	0.	0.	0.	6.2
137	Ca Al Si	0.	3.	19.	14.	0.	4.	0.	0.	52.	2.	5.	0.	0.	0.	0.	10.6
150	Ca Si Al	1.	3.	18.	22.	0.	4.	0.	0.	46.	2.	4.	0.	0.	0.	0.	14.4
21	Si Ca Al	2.	2.	22.	38.	0.	2.	0.	1.	29.	2.	3.	0.	0.	0.	0.	2.0
9	Al Si Ca	7.	0.	32.	30.	0.	1.	1.	0.	24.	2.	3.	0.	0.	0.	0.	0.8
27	Ca S Fe	0.	3.	6.	3.	0.	18.	0.	0.	58.	1.	10.	0.	1.	0.	0.	2.4
16	Ca Si S	0.	2.	9.	17.	0.	12.	0.	0.	54.	2.	3.	0.	0.	0.	0.	1.6
22	Ca S Si	0.	3.	9.	12.	0.	17.	0.	0.	53.	1.	4.	0.	0.	0.	0.	2.7
101	Ca Al Fe	0.	4.	18.	4.	0.	5.	0.	0.	58.	1.	9.	0.	0.	0.	0.	7.4
18	Ca Fe Al	0.	3.	12.	6.	0.	8.	0.	0.	55.	2.	14.	0.	0.	0.	0.	1.1
18	Si Al Na	19.	0.	28.	35.	0.	2.	1.	1.	11.	1.	2.	0.	0.	0.	0.	1.8
10	Si Ca Na	13.	1.	1.	55.	0.	2.	0.	0.	21.	1.	4.	0.	0.	0.	0.	1.4
7	Si Na Ca	17.	0.	0.	68.	0.	0.	0.	0.	10.	1.	4.	0.	0.	0.	0.	0.5
38	Ca Mg S	0.	20.	8.	2.	0.	13.	0.	0.	49.	1.	7.	0.	0.	0.	0.	2.5
40	Ca S Mg	0.	12.	8.	3.	0.	18.	0.	0.	51.	1.	6.	0.	0.	0.	0.	3.9
4	Si Al K	0.	0.	22.	54.	0.	1.	0.	10.	5.	2.	7.	0.	0.	0.	0.	0.5
49	Ca Mg Al	0.	21.	13.	4.	1.	6.	0.	0.	48.	1.	7.	0.	0.	0.	0.	2.7
56	Ca Al Mg	0.	12.	18.	3.	0.	6.	0.	0.	52.	1.	7.	0.	0.	0.	0.	3.5
40	Ca Mg Fe	0.	22.	9.	2.	0.	6.	0.	0.	47.	2.	12.	0.	0.	0.	0.	1.7
29	Ca Si Mg	0.	12.	5.	27.	0.	2.	0.	0.	48.	2.	4.	0.	0.	0.	0.	1.6
14	Ca Mg Si	0.	18.	9.	12.	0.	4.	0.	0.	52.	1.	4.	0.	0.	0.	0.	0.7
9	Si Ca Mg	0.	9.	2.	50.	0.	3.	0.	0.	31.	2.	4.	0.	0.	0.	0.	0.8

TABLE 4-19. - Arizona Eagle Butte ash on filter, Impactor #5, 23IM5 (Cont.)

100 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE 5.7

1185 TOTALS - 1. 5. 16. 16. 0. 8. 0. 1. 46. 1. 6. 0. 0. 0. 0. 100.0

SAMPLE #297 PSI/ARIZONA EAGLE BUTTE ash ON filter, Imp. #5, 23IM5.

NUMBER 1 DISK 32 FILE 101 - 104 PARTICLES

RUN 1 DATE 17-JUN-89 SUMMARY 104 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES Volume % 0.0-0.5 0.5-1.0 1.0- 2. 2.- 2. 2.- 3. 3.- 5. 5.-500.

Ca S Al 11.3 0. 1. 5. 17. 32. 26. 18.

Ca Al S 7.4 0. 2. 15. 22. 35. 26. 0.

Si Al Ca 6.2 0. 3. 15. 32. 30. 20. 0.

Ca Al Si 10.6 0. 5. 26. 20. 27. 16. 5.

Ca Si Al 14.4 0. 4. 20. 21. 26. 19. 10.

Ca Al Fe 7.4 0. 7. 22. 26. 35. 10. 0.

OTHERS - 42.7 0. 7. 17. 27. 32. 17. 0.

TOTALS - 100.0 0. 5. 17. 24. 31. 19. 4.

TABLE 4-20. - PSIT/MIT-2 Eagle Butte ash 1750 K. 7%. total filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSIT/MIT-2 EAGLE BUTTE ASH 1750K, 7%, TOTAL FILTER

NUMBER 3 DISK 29 FILE 109 - 112 PARTICLES

RUN 1 DATE 29-MAR-89 SUMMARY 112 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.24535E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
169	Si - -	0.	0.	0.	97.	0.	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	12.9
114	Ca - -	0.	5.	6.	3.	0.	0.	0.	0.	81.	0.	4.	0.	0.	0.	0.	12.3
8	Ca Fe -	0.	1.	0.	1.	0.	0.	0.	0.	80.	0.	17.	0.	0.	0.	0.	0.7
57	Si Ca -	0.	1.	0.	77.	0.	0.	0.	0.	20.	1.	1.	0.	0.	0.	0.	3.3
13	Ca Si -	0.	3.	3.	32.	0.	0.	0.	0.	57.	1.	3.	0.	0.	0.	0.	0.9
43	Al Si -	0.	0.	52.	47.	0.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	3.0
30	Si Al -	0.	0.	39.	56.	0.	0.	0.	1.	2.	0.	1.	0.	0.	0.	0.	2.7
54	Ca Al -	0.	3.	17.	1.	0.	0.	0.	0.	74.	0.	4.	0.	0.	0.	0.	5.2
2	Fe Si -	0.	0.	0.	20.	0.	0.	0.	3.	0.	0.	78.	0.	0.	0.	0.	0.6
9	Ca Mg -	0.	12.	3.	3.	0.	0.	0.	0.	78.	0.	3.	0.	0.	0.	0.	0.7
23	Si Al K	0.	0.	27.	51.	0.	2.	0.	12.	1.	0.	4.	0.	2.	0.	0.	0.8
39	Si Ca Al	1.	1.	14.	53.	0.	0.	0.	0.	28.	2.	1.	1.	0.	0.	0.	2.3
39	Si Al Ca	1.	0.	30.	48.	0.	0.	0.	2.	17.	1.	1.	0.	0.	0.	0.	2.7
19	Al Si Ca	0.	0.	44.	37.	0.	0.	0.	0.	18.	0.	0.	0.	0.	0.	0.	1.8
80	Ca Si Al	0.	2.	14.	24.	0.	0.	0.	0.	54.	2.	4.	0.	0.	0.	0.	7.3
86	Ca Al Si	0.	2.	20.	12.	0.	0.	0.	0.	61.	1.	4.	0.	0.	0.	0.	8.5
4	Si Al Fe	0.	0.	15.	69.	0.	0.	0.	4.	0.	4.	8.	0.	0.	0.	0.	0.6
4	Si Ca S	0.	0.	12.	44.	4.	13.	0.	1.	26.	1.	0.	0.	0.	0.	0.	0.5
1	Si S Ca	0.	0.	10.	46.	0.	24.	0.	0.	30.	0.	0.	0.	0.	0.	0.	0.5
15	Ca Si Fe	0.	4.	5.	18.	0.	0.	0.	0.	53.	2.	9.	0.	0.	0.	0.	1.1
90	Ca Al Mg	0.	8.	15.	2.	0.	0.	0.	0.	72.	1.	4.	0.	0.	0.	0.	8.2
38	Ca Mg Al	0.	14.	9.	3.	0.	0.	0.	0.	58.	0.	4.	0.	0.	0.	0.	3.2
4	Ca Si Ti	0.	3.	1.	24.	0.	0.	0.	0.	50.	9.	3.	0.	0.	0.	0.	0.6
9	Ca Fe Mg	0.	9.	6.	4.	0.	0.	0.	0.	58.	0.	13.	0.	0.	0.	0.	0.5
20	Ca Mg Fe	0.	18.	6.	2.	0.	0.	0.	0.	54.	0.	9.	0.	0.	0.	0.	1.5
17	Ca Al P	0.	0.	31.	1.	12.	0.	0.	0.	51.	2.	2.	0.	0.	0.	0.	1.3
7	Al Ca P	0.	0.	42.	0.	19.	0.	0.	0.	37.	2.	0.	0.	0.	0.	0.	1.1
11	Ca Fe Al	0.	5.	9.	1.	0.	0.	0.	0.	73.	1.	12.	0.	0.	0.	0.	1.2
52	Ca Al Fe	0.	4.	15.	3.	0.	0.	0.	0.	70.	0.	7.	0.	0.	0.	0.	5.5

TABLE 4-20. - PSIT/MIT-2 Eagle Butte ash 1750 K, 7%, total filter (Cont.)

16	Ca Si Mg	0.	9.	5.	22.	0.	0.	0.	0.	59.	1.	4.	0.	0.	0.	0.	1.6
21	Si Al Na	18.	0.	33.	41.	0.	0.	0.	1.	4.	0.	1.	0.	0.	0.	0.	1.4
3	Ca Al Ti	0.	3.	13.	3.	1.	0.	0.	0.	67.	8.	4.	0.	0.	0.	0.	0.7
81	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.9
1178	TOTALS -	0.	3.	14.	29.	0.	0.	0.	0.	46.	1.	5.	0.	0.	0.	0.	100.0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Si - -	12.9	4.	25.	14.	29.	20.	8.	0.
Ca - -	12.3	4.	22.	29.	39.	4.	0.	0.
Ca Al -	5.2	6.	39.	41.	11.	2.	0.	0.
Ca Al Mg	8.2	9.	40.	36.	14.	1.	0.	0.
Ca Si Al	7.3	9.	25.	30.	30.	6.	1.	0.
Ca Al Si	8.5	9.	43.	29.	18.	1.	0.	0.
Ca Al Fe	5.5	17.	32.	25.	26.	1.	0.	0.
OTHERS -	40.0	11.	23.	20.	30.	14.	1.	0.
TOTALS -	100.0	9.	28.	25.	28.	9.	1.	0.

**TABLE 4-21. - PSIT pure ash on filter. Kentucky #9, #1G-A, 0.2 g/min.
7% O₂, 1500 K**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 243 PSI PURE ASH ON FILTER, KY#9, #1G-A, 0.2G/MIN, 7%O₂, 2350F
NUMBER 243 DISK 43 FILE 115 - 118 PARTICLES
RUN 1 DATE 27-FEB-90 SUMMARY 118 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.49233E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
133	Si - -	0.	0.	2.	92.	0.	0.	0.	2.	1.	1.	1.	0.	1.	0.	0.	13.0
28	Fe - -	0.	0.	1.	5.	0.	0.	0.	0.	0.	0.	95.	0.	0.	0.	0.	2.8
201	Si Al -	0.	0.	33.	61.	0.	0.	0.	3.	1.	1.	2.	0.	0.	0.	0.	16.6
13	Al Si -	0.	0.	51.	47.	0.	0.	0.	0.	0.	0.	2.	0.	0.	0.	0.	2.0
14	Fe Si -	0.	0.	3.	16.	0.	0.	0.	1.	1.	0.	79.	0.	1.	0.	0.	1.6
9	Si Na -	17.	0.	2.	69.	0.	0.	0.	5.	2.	4.	0.	0.	1.	0.	0.	0.8
28	Fe Si Al	0.	0.	13.	28.	0.	0.	0.	4.	2.	2.	51.	0.	0.	0.	0.	2.1
134	Si Al Fe	0.	0.	26.	52.	0.	0.	0.	7.	2.	1.	12.	0.	0.	0.	0.	14.7
25	Si Fe Al	0.	2.	18.	44.	0.	0.	0.	6.	1.	2.	27.	0.	0.	0.	0.	2.1
402	Si Al K	0.	0.	29.	55.	0.	0.	0.	10.	1.	1.	4.	0.	0.	0.	0.	33.5
21	Si Al Ti	0.	0.	26.	55.	0.	0.	0.	5.	2.	9.	3.	0.	0.	0.	0.	1.6
17	Si Al Ca	0.	0.	28.	50.	0.	0.	0.	5.	12.	1.	4.	0.	0.	0.	0.	2.1
8	Si Ca Al	2.	0.	14.	59.	0.	1.	0.	2.	19.	0.	1.	0.	2.	0.	0.	1.1
11	Si Na K	18.	0.	1.	67.	0.	0.	0.	7.	2.	3.	0.	0.	2.	0.	0.	1.0
8	Si Na Al	19.	0.	7.	65.	0.	0.	0.	3.	2.	2.	0.	0.	1.	0.	0.	0.7
106	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.0
1158	TOTALS -	1.	0.	23.	58.	0.	0.	0.	6.	2.	1.	10.	0.	1.	0.	0.	100.0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Si - -	13.0	5.	30.	32.	31.	2.	0.	0.
Si Al -	16.6	3.	16.	34.	42.	6.	0.	0.
Si Al K	33.5	2.	15.	38.	39.	6.	0.	0.
Si Al Fe	14.7	3.	20.	31.	44.	2.	0.	0.
OTHERS -	22.2	9.	29.	30.	30.	3.	0.	0.
TOTALS -	100.0	4.	21.	33.	37.	4.	0.	0.

TABLE 4-22. - PSIT pure ash on filter, Kentucky #9 PSIT #1i, 0.2 g/min.
21% O₂, 1500 K

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE #245 PSI PURE ASH ON FILTER, KY#9 PSI #1i, 0.2G/MIN, 21%O2, 2350F
 NUMBER 245 DISK 43 FILE 119 - 122 PARTICLES
 RUN 1 DATE 27-FEB-90 SUMMARY 122 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.38517E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
38	Fe - -	0.	0.	1.	4.	0.	0.	0.	0.	0.	0.	95.	0.	0.	0.	0.	2.4
141	Si - -	0.	0.	2.	93.	0.	0.	0.	2.	1.	1.	1.	0.	1.	0.	0.	12.9
154	Si Al -	0.	0.	31.	63.	0.	0.	0.	3.	0.	1.	2.	0.	0.	0.	0.	12.7
14	Al Si -	0.	0.	51.	47.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	1.3
24	Fe Si -	0.	0.	2.	19.	0.	0.	0.	2.	1.	0.	75.	0.	0.	0.	0.	1.9
11	Si K -	0.	0.	0.	87.	0.	0.	0.	13.	0.	0.	0.	0.	0.	0.	0.	0.7
7	Si Na -	23.	0.	3.	67.	0.	2.	0.	3.	1.	1.	0.	0.	0.	0.	0.	0.6
372	Si Al K	0.	0.	29.	55.	0.	0.	0.	10.	1.	1.	4.	0.	0.	0.	0.	32.6
6	Si K Al	0.	0.	12.	61.	0.	0.	0.	17.	1.	2.	3.	0.	3.	0.	0.	0.6
153	Si Al Fe	0.	0.	27.	52.	0.	0.	0.	6.	1.	2.	12.	0.	0.	0.	0.	14.6
33	Si Fe Al	0.	0.	19.	44.	0.	0.	0.	7.	2.	3.	25.	0.	0.	0.	0.	3.0
32	Fe Si Al	0.	0.	14.	28.	0.	0.	0.	3.	0.	1.	53.	0.	0.	0.	0.	3.2
4	Si Al Zn	0.	0.	18.	72.	0.	0.	0.	0.	0.	0.	0.	0.	9.	0.	0.	0.5
26	Si Al Ti	0.	0.	27.	47.	0.	0.	0.	7.	3.	11.	5.	0.	0.	0.	0.	3.1
6	Si Ti Al	0.	0.	20.	37.	0.	0.	0.	8.	3.	26.	7.	0.	0.	0.	0.	0.5
20	Si Al Ca	0.	0.	27.	49.	0.	1.	0.	4.	13.	0.	4.	0.	2.	0.	0.	1.4
7	Si Na Al	23.	0.	7.	65.	0.	0.	0.	0.	0.	2.	1.	0.	1.	0.	0.	0.9
2	Fe Si Ca	0.	0.	6.	20.	0.	0.	0.	0.	7.	2.	66.	0.	0.	0.	0.	0.5
103	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.3
1153	TOTALS -	1.	0.	21.	57.	0.	0.	0.	6.	1.	2.	11.	0.	0.	0.	0.	100.0

**TABLE 4-22. - PSIT pure ash on filter, Kentucky #9 PSIT #1i, 0.2 g/min.
21% O₂, 1500 K (Cont.)**

SAMPLE #245 PSI PURE ASH ON FILTER, KY#9 PSI #1i, 0.2G/MIN, 21%O₂, 2350F
 NUMBER 245 DISK 43 FILE 119 - 122 PARTICLES
 RUN 1 DATE 27-FEB-90 SUMMARY 122 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	12.9	12.	32.	34.	19.	3.	0.	0.
Si Al -	12.7	3.	18.	37.	34.	8.	0.	0.
Si Al K	32.6	3.	21.	38.	32.	6.	0.	0.
Si Al Fe	14.6	4.	33.	32.	26.	5.	0.	0.
OTHERS -	27.2	13.	29.	31.	24.	5.	0.	0.
TOTALS -	100.0	7.	26.	35.	27.	5.	0.	0.

TABLE 4-23. - PSIT/MIT-4 Kentucky #9 ash, 1750 K, 7% O₂, total filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI/MIT-4 KY #9 ASH, 1750K, 7%O2, TOTAL FILTER
 NUMBER 4 DISK 29 FILE 113 - 116 PARTICLES
 RUN 1 DATE 30-MAR-89 SUMMARY 116 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.21494E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Fe - -	0.	0.	0.	4.	0.	0.	0.	0.	0.	0.	95.	0.	0.	0.	0.	3.3
93	Si - -	0.	0.	2.	97.	0.	0.	0.	1.	0.	0.	1.	0.	0.	0.	0.	10.5
40	Ca - -	0.	0.	0.	1.	0.	0.	1.	0.	97.	0.	1.	0.	0.	0.	0.	2.7
184	Si Al -	0.	0.	29.	65.	0.	0.	0.	3.	0.	0.	1.	0.	0.	0.	0.	18.5
14	Al Si -	0.	0.	54.	46.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	2.1
10	Fe Si -	0.	0.	3.	25.	0.	1.	0.	2.	0.	1.	68.	1.	0.	0.	0.	0.7
371	Si Al K	0.	0.	31.	54.	0.	0.	0.	10.	1.	1.	3.	0.	0.	0.	0.	34.5
141	Si Al Fe	0.	0.	28.	51.	0.	0.	0.	5.	2.	2.	12.	0.	0.	0.	0.	11.8
39	Fe Si Al	0.	0.	11.	28.	0.	1.	0.	2.	2.	1.	55.	0.	0.	0.	0.	2.8
37	Si Fe Al	1.	0.	16.	46.	0.	0.	0.	5.	2.	2.	28.	0.	0.	0.	0.	2.2
29	Si Al Ca	0.	0.	24.	58.	0.	0.	0.	3.	9.	1.	3.	0.	0.	0.	0.	2.4
8	Si Ca Al	0.	0.	23.	42.	0.	0.	0.	0.	30.	1.	4.	0.	0.	0.	0.	1.2
27	Si Al Ti	0.	0.	27.	52.	0.	0.	0.	4.	2.	10.	3.	0.	0.	0.	0.	1.9
92	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.2
1133	TOTALS -	0.	0.	23.	55.	0.	1.	0.	5.	5.	1.	10.	0.	0.	0.	0.	100.0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Si - -	10.5	2.	18.	33.	41.	4.	1.	0.
Si Al -	18.5	4.	26.	19.	40.	9.	1.	0.
Si Al K	34.5	3.	20.	24.	40.	11.	2.	0.
Si Al Fe	11.8	7.	19.	31.	34.	7.	1.	0.
OTHERS -	14.8	7.	16.	24.	37.	16.	0.	0.
TOTALS -	100.0	5.	20.	25.	39.	11.	1.	0.

TABLE 4-24. - Arizona, Kentucky #9 ash on filter, 24IM1A, impactor #1

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 302 PSI/ARIZONA, KY#9 ASH ON FILTER, 24IM1A, IMPACTOR #1
 NUMBER 302 DISK 45 FILE 101 - 104 PARTICLES
 RUN 1 DATE 2-MAR-90 SUMMARY 104 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.10495E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Ca - -	0.	0.	1.	1.	0.	4.	1.	0.	92.	0.	1.	0.	0.	0.	0.	4.7
111	Si - -	0.	0.	2.	92.	0.	0.	0.	3.	1.	0.	1.	0.	0.	0.	0.	11.3
52	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	1.	0.	97.	0.	0.	0.	0.	4.4
10	Al Si -	0.	0.	52.	46.	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	0.	0.6
66	Si Al -	0.	0.	30.	63.	0.	0.	0.	4.	1.	1.	1.	0.	0.	0.	0.	6.2
7	Fe Si -	0.	0.	2.	16.	0.	0.	0.	0.	1.	0.	81.	0.	0.	0.	0.	0.9
28	Ca S -	0.	0.	0.	2.	0.	29.	0.	0.	69.	0.	0.	0.	0.	0.	0.	2.6
157	Si Al Fe	0.	0.	27.	49.	0.	1.	0.	6.	3.	1.	12.	0.	0.	0.	0.	10.5
19	Si Fe Al	0.	0.	17.	46.	0.	0.	0.	7.	2.	2.	26.	0.	0.	0.	0.	2.1
26	Fe Si Al	0.	0.	11.	26.	0.	1.	0.	2.	3.	1.	56.	0.	0.	0.	0.	2.7
311	Si Al K	0.	0.	28.	56.	0.	0.	0.	10.	1.	0.	4.	0.	0.	0.	0.	28.0
7	Si Fe K	0.	0.	7.	50.	0.	0.	0.	14.	3.	2.	24.	0.	1.	0.	0.	0.6
8	Fe Si K	0.	0.	6.	25.	0.	0.	3.	12.	5.	2.	47.	0.	0.	0.	0.	1.1
73	Si Al Ca	0.	0.	24.	47.	0.	4.	0.	5.	14.	2.	4.	0.	0.	0.	0.	6.5
18	Ca Si Al	0.	1.	16.	26.	0.	7.	0.	1.	42.	1.	6.	0.	0.	0.	0.	1.9
20	Si Ca Al	0.	0.	16.	49.	0.	3.	0.	2.	27.	.	3.	0.	0.	0.	0.	1.3
20	Si Al Ti	0.	0.	28.	48.	0.	0.	0.	6.	1.	11.	5.	0.	0.	0.	0.	1.2
23	Ca S Si	0.	0.	4.	12.	0.	20.	0.	0.	60.	0.	3.	0.	0.	0.	0.	2.4
16	Si Al S	0.	0.	25.	49.	0.	14.	0.	1.	7.	1.	3.	0.	2.	0.	0.	1.8
2	Si S Ti	0.	0.	0.	49.	0.	18.	0.	0.	10.	15.	7.	0.	0.	0.	0.	0.8
140	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																7.9
1162	TOTALS -	0.	0.	18.	47.	0.	3.	0.	5.	13.	1.	12.	0.	0.	0.	0.	100.0

TABLE 4-24. - Arizona, Kentucky #9 ash on filter, 24IM1A, impactor #1 (Cont.)

SAMPLE # 302 PSI/ARIZONA, KY#9 ASH ON FILTER, 24IM1A, IMPACTOR #1
 NUMBER 302 DISK 45 FILE 101 - 104 PARTICLES
 RUN 1 DATE 2-MAR-90 SUMMARY 104 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	4.7	7.	17.	16.	44.	16.	0.	0.
Si - -	11.3	1.	21.	21.	43.	15.	0.	0.
Fe - -	4.4	5.	5.	26.	45.	20.	0.	0.
Si Al -	6.2	4.	12.	12.	50.	22.	0.	0.
Si Al K	28.0	3.	8.	22.	37.	27.	4.	0.
Si Al Ca	6.5	4.	22.	23.	38.	14.	0.	0.
Si Al Fe	10.5	15.	33.	11.	20.	15.	5.	0.
OTHERS -	28.3	6.	18.	14.	37.	24.	1.	0.
TOTALS -	100.0	5.	16.	18.	37.	22.	2.	0.

TABLE 4-25. - PSIT K-7 8/4/88 Kentucky #11. 7% O₂. 1500 K

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI K-7 8/4/88 ky#11 7%O2 1500K

NUMBER 0 DISK 17 FILE 110 - 113 PARTICLES
 RUN 3 DATE 8/4/88 SUMMARY 113 TOTAL 1199
 BLOCKS 0 TIME 1930 OFF-PT. 48.00 >>500U 0

TOTAL Volume FACTOR: 0.53163E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Fe - -	0.	0.	0.	3.	0.	1.	0.	0.	2.	0.	92.	0.	1.	0.	0.	2.9
84	Si - -	0.	0.	4.	93.	0.	0.	0.	1.	0.	0.	1.	0.	0.	0.	0.	11.2
31	Ca - -	1.	0.	0.	2.	0.	2.	0.	0.	93.	0.	1.	0.	0.	0.	0.	2.2
169	Si Al -	0.	0.	27.	63.	0.	0.	0.	4.	1.	1.	2.	0.	0.	0.	0.	17.1
24	Al Si -	0.	0.	52.	44.	0.	0.	0.	1.	0.	1.	1.	0.	0.	0.	0.	2.2
4	Si Fe -	0.	0.	3.	71.	0.	0.	0.	3.	0.	0.	20.	0.	2.	0.	0.	0.8
22	Si Fe Al	1.	1.	14.	44.	0.	1.	0.	7.	2.	1.	25.	2.	2.	0.	0.	1.8
172	Si Al Fe	0.	0.	27.	51.	0.	0.	0.	7.	2.	1.	11.	0.	1.	0.	0.	19.2
26	Fe Si Al	0.	0.	14.	24.	0.	0.	1.	5.	2.	2.	50.	1.	1.	0.	0.	3.0
303	Si Al K	0.	1.	29.	53.	0.	0.	0.	9.	1.	1.	4.	0.	1.	0.	0.	24.7
10	Al Si K	0.	0.	46.	44.	0.	0.	0.	7.	0.	1.	1.	0.	0.	0.	0.	0.9
13	Si Al S	0.	0.	21.	54.	0.	9.	1.	4.	4.	0.	3.	1.	4.	0.	0.	0.7
12	Si Al Ti	2.	1.	27.	42.	0.	0.	0.	5.	3.	11.	7.	1.	0.	0.	0.	0.9
3	Ti Si Al	0.	0.	16.	28.	0.	0.	0.	6.	0.	43.	8.	0.	0.	0.	0.	0.5
30	Si Al Ca	0.	1.	24.	48.	0.	1.	0.	7.	11.	1.	5.	0.	1.	0.	0.	3.2
8	Ca Si Al	0.	1.	13.	25.	0.	1.	0.	2.	54.	0.	4.	0.	0.	0.	0.	1.4
23	Si Al Na	11.	0.	26.	48.	0.	3.	1.	6.	1.	1.	3.	0.	2.	0.	0.	1.8
4	Ca Si Fe	0.	3.	5.	26.	0.	3.	0.	0.	52.	2.	11.	0.	0.	0.	0.	0.6
4	Fe Si K	0.	0.	3.	17.	0.	0.	0.	7.	0.	2.	68.	0.	3.	0.	0.	0.5
75	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.4
1065	TOTALS -	1.	0.	22.	53.	0.	1.	0.	5.	5.	2.	10.	0.	1.	0.	0.	100.0

TABLE 4-25. - PSIT K-7 8/4/88 Kentucky #11, 7% O₂, 1500 K (Cont.)

SAMPLE PSI K-7 8/4/88 ky#11 7%O2 1500K

NUMBER 0 DISK 17 FILE 110 - 113 PARTICLES
 RUN 3 DATE 8/4/88 SUMMARY 113 TOTAL 1199
 BLOCKS 0 TIME 1930 OFF-PT. 48.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.2-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	11.2	2.	12.	5.	80.	1.	0.	0.
Si Al -	17.1	1.	13.	8.	73.	4.	1.	0.
Si Al K	24.7	2.	20.	11.	61.	5.	1.	0.
Si Al Fe	19.2	2.	21.	11.	64.	2.	0.	0.
OTHERS -	27.8	3.	13.	12.	67.	4.	1.	0.
TOTALS -	100.0	2.	16.	10.	67.	4.	1.	0.

TABLE 4-26. - Arizona, Kentucky #11, ash on filter, 27IM1E, impactor #1

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 311 PSI/ARIZONA, KY#11, ASH ON FILTER, 27IM1E, IMPACTOR #1
 NUMBER 311 DISK 45 FILE 105 - 108 PARTICLES
 RUN 1 DATE 3-MAR-90 SUMMARY 108 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.19245E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
136	Si - -	0.	0.	2.	93.	0.	0.	0.	2.	1.	0.	1.	0.	0.	0.	0.	14.0
75	Ca - -	0.	0.	1.	3.	0.	4.	1.	0.	90.	0.	2.	0.	0.	0.	0.	5.9
43	Fe - -	0.	0.	0.	3.	0.	0.	0.	0.	1.	0.	95.	0.	0.	0.	0.	3.5
88	Si Al -	0.	0.	28.	63.	0.	0.	0.	4.	2.	0.	3.	0.	0.	0.	0.	9.1
12	Al Si -	0.	0.	50.	45.	0.	0.	0.	3.	0.	0.	1.	0.	0.	0.	0.	1.2
8	Fe Si -	0.	0.	3.	15.	0.	0.	0.	1.	0.	0.	82.	0.	0.	0.	0.	1.0
39	Ca S -	0.	0.	0.	1.	0.	21.	0.	0.	76.	0.	0.	0.	0.	0.	0.	2.9
309	Si Al K	0.	0.	27.	58.	0.	0.	0.	9.	1.	1.	4.	0.	0.	0.	0.	27.6
12	Si K Al	0.	0.	11.	68.	0.	2.	0.	12.	1.	0.	4.	0.	0.	0.	0.	0.7
150	Si Al Fe	0.	0.	27.	51.	0.	0.	0.	7.	3.	1.	11.	0.	0.	0.	0.	9.8
14	Fe Si Al	0.	0.	11.	20.	0.	0.	0.	1.	3.	0.	64.	0.	0.	0.	0.	0.9
36	Si Fe Al	0.	0.	13.	52.	0.	0.	0.	6.	2.	2.	25.	0.	0.	0.	0.	4.5
15	Si Ca Al	0.	0.	19.	42.	0.	2.	0.	1.	28.	2.	6.	0.	0.	0.	0.	1.5
41	Si Al Ca	1.	0.	26.	49.	0.	2.	0.	5.	12.	1.	4.	0.	0.	0.	0.	2.1
20	Ca Si Al	1.	0.	16.	26.	0.	7.	0.	0.	43.	1.	4.	0.	0.	0.	0.	2.0
24	Si Al S	0.	0.	24.	48.	0.	13.	0.	3.	7.	1.	4.	0.	0.	0.	0.	1.1
6	Si Ca S	0.	0.	12.	44.	0.	14.	0.	4.	21.	0.	4.	0.	2.	0.	0.	0.7
18	Ca S Si	0.	0.	4.	11.	0.	22.	0.	1.	60.	0.	3.	0.	0.	0.	0.	1.9
10	Ca Si S	0.	2.	8.	21.	0.	14.	1.	1.	47.	0.	6.	0.	0.	0.	0.	1.0
7	Si Al Ti	0.	0.	24.	52.	0.	0.	0.	6.	3.	10.	6.	0.	0.	0.	0.	0.6
3	Si Ti Al	0.	0.	16.	53.	0.	0.	0.	6.	0.	19.	6.	0.	0.	0.	0.	0.6
10	Ca S Al	0.	2.	11.	5.	0.	23.	0.	0.	56.	0.	3.	0.	1.	0.	0.	0.8
2	Si Ti Ca	0.	0.	13.	45.	0.	1.	0.	3.	14.	18.	6.	0.	0.	0.	0.	0.8
88	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.2
1166	TOTALS -	0.	0.	17.	50.	0.	3.	0.	5.	14.	1.	10.	0.	0.	0.	0.	100.0

TABLE 4-26. - Arizona, Kentucky #11, ash on filter, 27IM1E, impactor #1 (Cont.)

SAMPLE # 311 PSI/ARIZONA, KY#11, ASH ON FILTER, 27IM1E, IMPACTOR #1
 NUMBER 311 DISK 45 FILE 105 - 108 PARTICLES
 RUN 1 DATE 3-MAR-90 SUMMARY 108 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	14.0	5.	27.	27.	32.	8.	1.	0.
Ca - -	5.9	18.	21.	18.	35.	8.	0.	0.
Si Al -	9.1	6.	22.	13.	48.	11.	1.	0.
Si Al K	27.6	5.	24.	28.	29.	12.	1.	0.
Si Al Fe	9.8	23.	23.	26.	18.	9.	2.	0.
Si Fe Al	4.5	4.	18.	18.	53.	8.	0.	0.
OTHERS -	29.1	9.	26.	29.	23.	13.	1.	0.
TOTALS -	100.0	9.	24.	26.	30.	11.	1.	0.

TABLE 4-27. - Arizona Upper Freeport ash, 32IM1, impactor #1

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 117 PSI/ARIZONA Upper Freeport ash, 32IM1, impactor # 1.

NUMBER 117 DISK 43 FILE 107 - 110 PARTICLES

RUN 1 DATE 16-FEB-90 SUMMARY 110 TOTAL 1023

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.15770E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
73	Si - -	0.	0.	3.	92.	0.	0.	0.	3.	0.	0.	1.	0.	0.	0.	0.	7.7
33	Ca - -	0.	0.	0.	1.	0.	2.	1.	0.	96.	0.	0.	0.	0.	0.	0.	3.0
18	Fe - -	0.	0.	1.	4.	0.	0.	0.	1.	1.	0.	92.	0.	0.	0.	0.	1.3
8	Fe Si -	0.	0.	2.	18.	0.	0.	0.	1.	1.	0.	77.	0.	0.	0.	0.	0.5
15	Al Si -	0.	0.	52.	47.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	1.4
82	Si Al -	0.	0.	34.	63.	0.	0.	0.	2.	0.	0.	1.	0.	0.	0.	0.	9.0
6	Ca S -	0.	0.	0.	0.	0.	33.	0.	0.	66.	0.	0.	0.	0.	0.	0.	0.5
369	Si Al K	0.	0.	30.	55.	0.	0.	0.	10.	1.	1.	3.	0.	0.	0.	0.	40.4
12	Al Si K	0.	0.	47.	41.	0.	0.	0.	10.	0.	1.	1.	0.	0.	0.	0.	0.8
42	Si Al Ca	0.	0.	31.	48.	0.	0.	0.	5.	11.	2.	3.	0.	0.	0.	0.	4.6
7	Si Ca Al	0.	0.	20.	40.	0.	0.	0.	4.	27.	1.	7.	0.	0.	0.	0.	1.3
11	Ca Si Al	0.	0.	11.	24.	1.	2.	1.	0.	59.	0.	3.	0.	0.	0.	0.	1.7
109	Si Al Fe	0.	0.	30.	48.	0.	0.	0.	6.	2.	1.	13.	0.	0.	0.	0.	14.4
14	Si Fe Al	0.	1.	20.	43.	0.	0.	0.	5.	1.	3.	28.	0.	0.	0.	0.	0.8
31	Fe Si Al	0.	1.	16.	27.	0.	0.	0.	4.	1.	1.	50.	0.	0.	0.	0.	2.3
4	Al Si Fe	0.	0.	44.	40.	0.	0.	0.	6.	1.	1.	8.	0.	0.	0.	0.	0.5
16	Si Al Ti	0.	0.	30.	48.	0.	0.	0.	5.	4.	10.	3.	0.	0.	0.	0.	2.1
6	Ca Fe Si	0.	0.	8.	17.	0.	4.	0.	0.	48.	3.	22.	0.	0.	0.	0.	1.0
2	Ca Si Fe	0.	0.	1.	12.	0.	0.	0.	0.	79.	0.	9.	0.	0.	0.	0.	0.8
56	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.6
914	TOTALS -	0.	0.	25.	50.	0.	1.	1.	6.	9.	1.	7.	0.	0.	0.	0.	100.0

TABLE 4-27. - Arizona Upper Freeport ash, 32IM1, impactor #1 (Cont.)

SAMPLE # 117 PSI/ARIZONA Upper Freeport ash, 32IM1, impactor # 1.
 NUMBER 117 DISK 43 FILE 107 - 110 PARTICLES
 RUN 1 DATE 16-FEB-90 SUMMARY 110 TOTAL 1023
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	7.7	3.	13.	26.	42.	12.	4.	0.
Si AL -	9.0	0.	15.	20.	46.	19.	0.	0.
Si AL K	40.4	2.	12.	22.	45.	15.	3.	0.
Si AL Ca	4.6	4.	30.	25.	34.	7.	0.	0.
Si AL Fe	14.4	4.	20.	19.	47.	7.	2.	0.
OTHERS -	23.8	2.	21.	27.	31.	16.	3.	0.
TOTALS -	100.0	2.	16.	23.	41.	14.	3.	0.

TABLE 4-28. - Arizona Upper Freeport ash, 32IM3, impactor #3

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 119 PSI/ARIZONA UPPER FREEPORT ASH, 32IM3, IMPACTOR #3
 NUMBER 119 DISK 43 FILE 111 - 114 PARTICLES
 RUN 1 DATE 17-FEB-90 SUMMARY 114 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.35896E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Si - -	0.	0.	2.	94.	0.	0.	0.	3.	0.	0.	0.	0.	0.	0.	0.	4.5
8	Fe - -	0.	0.	2.	2.	0.	0.	0.	0.	0.	0.	96.	0.	0.	0.	0.	0.8
135	Si Al -	0.	0.	38.	58.	0.	0.	0.	2.	0.	0.	1.	0.	0.	0.	0.	13.2
18	Al Si -	0.	0.	49.	46	0.	0.	0.	2.	0.	1.	0.	0.	0.	0.	0.	1.0
79	Ca S -	0.	0.	0.	1.	0.	45.	0.	0.	53.	0.	0.	0.	0.	0.	0.	8.9
3	Si Mg -	0.	26.	0.	74.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.6
445	Si Al K	0.	0.	33.	52.	0.	0.	0.	10.	1.	0.	2.	0.	1.	0.	0.	41.7
4	Al Si K	0.	0.	48.	41.	0.	0.	0.	8.	1.	1.	1.	0.	1.	0.	0.	0.5
28	Si Al S	0.	0.	35.	51.	0.	11.	0.	1.	1.	0.	1.	0.	0.	0.	0.	1.7
16	Si Al Ti	0.	0.	27.	54.	0.	0.	0.	4.	1.	12.	2.	0.	0.	0.	0.	0.9
10	Fe Si Al	0.	0.	16.	26.	0.	1.	0.	2.	2.	2.	49.	1.	0.	0.	0.	0.6
97	Si Al Fe	0.	0.	31.	48.	0.	0.	0.	6.	2.	1.	11.	0.	0.	0.	0.	9.5
13	Si Fe Al	0.	0.	18.	47.	0.	0.	0.	5.	0.	2.	27.	0.	1.	0.	0.	0.7
14	Ca S Si	0.	0.	6.	15.	0.	33.	0.	0.	43.	0.	1.	0.	0.	0.	0.	1.2
58	Si Al Ca	0.	0.	28.	49.	0.	2.	0.	4.	12.	1.	3.	0.	1.	0.	0.	5.5
4	Ca S Fe	0.	0.	1.	2.	0.	24.	0.	0.	59.	0.	13.	0.	0.	0.	0.	0.8
8	Si Al Zn	0.	0.	33.	55.	0.	4.	0.	0.	0.	0.	0.	0.	9.	0.	0.	1.0
2	Si Na Ca	26.	0.	3.	62.	0.	0.	0.	0.	7.	0.	0.	0.	2.	0.	0.	0.6
1	Si Ca Mg	0.	24.	0.	36.	0.	9.	0.	0.	31.	0.	0.	0.	0.	0.	0.	0.7
84	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.2
1075	TOTALS -	0.	0.	27.	47.	0.	6.	0.	5.	9.	1.	4.	0.	1.	0.	0.	100.0

TABLE 4-28. - Arizona Upper Freeport ash, 32IM3, impactor #3 (Cont.)

SAMPLE # 119 PSI/ARIZONA UPPER FREEPORT ASH, 32IM3, IMPACTOR #3
 NUMBER 119 DISK 43 FILE 111 - 114 PARTICLES
 RUN 1 DATE 17-FEB-90 SUMMARY 114 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	4.5	23.	37.	35.	0.	2.	3.	0.
Si Al -	13.2	19.	33.	31.	8.	5.	4.	0.
Ca S -	8.9	8.	34.	42.	14.	1.	0.	0.
Si Al K	41.7	18.	42.	26.	6.	5.	3.	0.
Si Al Ca	5.5	19.	31.	40.	7.	3.	1.	0.
Si Al Fe	9.5	35.	32.	20.	10.	1.	2.	0.
OTHERS -	16.7	15.	29.	28.	16.	9.	4.	0.
TOTALS -	100.0	19.	36.	29.	9.	5.	3.	0.

TABLE 4-29. - PSIT/MIT-3 Upper Freeport ash, 1750 K, 7% O₂, total filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PS1/MIT-3 UPPER FREEPORT ASH, 1750K, 7%O2, TOTAL FILTER
 NUMBER 2 DISK 29 FILE 105 - 108 PARTICLES
 RUN 1 DATE 29-MAR-89 SUMMARY 108 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.16271E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
83	Si - -	0.	0.	2.	95.	0.	0.	0.	2.	0.	0.	1.	0.	0.	0.	0.	8.8
48	Ca - -	0.	0.	1.	2.	0.	1.	1.	0.	94.	0.	1.	0.	0.	0.	0.	3.7
17	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	98.	0.	0.	0.	0.	1.5
174	Si Al -	0.	0.	35.	61.	0.	0.	0.	3.	0.	0.	1.	0.	0.	0.	0.	16.4
18	Al Si -	0.	0.	51.	47.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	1.6
4	Fe Si -	0.	0.	4.	15.	0.	0.	0.	1.	2.	0.	78.	0.	0.	0.	0.	0.5
22	Fe Si Al	0.	0.	13.	25.	0.	0.	0.	3.	1.	0.	57.	0.	0.	0.	0.	1.8
29	Si Fe Al	0.	0.	16.	47.	0.	1.	0.	6.	1.	2.	27.	0.	0.	0.	0.	1.8
87	Si Al Fe	0.	0.	29.	49.	0.	0.	0.	7.	1.	1.	12.	0.	0.	0.	0.	7.1
471	Si Al K	0.	0.	33.	54.	0.	0.	0.	10.	1.	1.	2.	0.	0.	0.	0.	44.7
9	Al Si K	0.	0.	44.	40.	0.	1.	0.	10.	0.	0.	5.	0.	0.	0.	0.	0.8
36	Al Ti	0.	0.	34.	49.	0.	0.	0.	3.	1.	11.	1.	0.	0.	0.	0.	1.8
2	Ca Fe Si	0.	0.	0.	12.	0.	0.	0.	4.	56.	4.	23.	0.	0.	0.	0.	0.5
47	Si Al Ca	0.	0.	32.	48.	0.	0.	0.	3.	11.	1.	3.	0.	0.	0.	0.	3.0
11	Si Al S	0.	0.	32.	50.	3.	12.	1.	2.	0.	0.	0.	0.	0.	0.	0.	0.7
3	Si Al Cu	0.	0.	33.	54.	0.	0.	0.	2.	2.	0.	2.	8.	0.	0.	0.	0.6
88	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.2
1149	TOTALS -	0.	0.	27.	53.	0.	0.	0.	6.	5.	1.	6.	0.	0.	0.	0.	100.0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	8.8	5.	10.	25.	48.	10.	3.	0.
Si Al -	16.4	10.	34.	23.	24.	8.	1.	0.
Si Al K	44.7	8.	20.	17.	32.	17.	5.	0.
Si Al Fe	7.1	10.	28.	23.	19.	14.	6.	0.
OTHERS -	23.0	15.	23.	20.	24.	16.	2.	0.
TOTALS -	100.0	10.	23.	20.	30.	15.	4.	0.

**TABLE 4-30. - PSIT pure ash on filter Illinois #6. #if. 7% O₂.
0.2 g/min. 1500 K**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 246 PSI PURE ASH on filter ILL#6, #if, 7%O₂, 0.2g/min, 2350F
NUMBER 246 DISK 43 FILE 123 - 126 PARTICLES
RUN 1 DATE 28-FEB-90 SUMMARY 126 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.24960E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
174	Si - -	1.	0.	3.	90.	0.	0.	0.	2.	1.	1.	1.	0.	1.	0.	0.	17.1
35	Fe - -	0.	0.	2.	4.	0.	0.	0.	0.	1.	0.	93.	0.	0.	0.	0.	2.3
10	Ca - -	0.	0.	2.	5.	0.	1.	5.	0.	83.	0.	5.	0.	0.	0.	0.	0.6
7	Al - -	0.	0.	91.	2.	0.	5.	0.	1.	1.	0.	0.	0.	0.	0.	0.	1.5
11	Si Fe -	0.	0.	3.	65.	0.	0.	0.	1.	0.	2.	30.	0.	0.	0.	0.	1.1
22	Fe Si -	0.	0.	2.	23.	0.	0.	0.	2.	2.	0.	70.	0.	0.	0.	0.	2.2
156	Si Al -	0.	0.	30.	63.	0.	0.	0.	4.	1.	1.	2.	0.	0.	0.	0.	13.4
11	Al Si -	0.	0.	54.	45.	0.	0.	0.	0.	0.	0.	1.	0.	0.	0.	0.	1.2
5	Ca S -	0.	0.	0.	0.	0.	13.	5.	0.	83.	0.	0.	0.	0.	0.	0.	0.7
9	Si Ca -	0.	0.	2.	74.	0.	2.	0.	0.	23.	0.	0.	0.	0.	0.	0.	0.7
26	Si Na -	20.	0.	3.	67.	0.	0.	0.	4.	2.	2.	0.	0.	1.	0.	0.	2.3
11	Si K -	0.	0.	1.	84.	0.	0.	0.	11.	0.	3.	0.	1.	0.	0.	0.	0.7
102	Si Al Fe	0.	0.	25.	52.	0.	0.	0.	6.	4.	1.	11.	0.	0.	0.	0.	10.1
39	Si Fe Al	0.	0.	15.	48.	0.	0.	0.	4.	3.	1.	28.	0.	0.	0.	0.	3.6
29	Fe Si Al	0.	0.	11.	22.	0.	0.	0.	2.	4.	1.	60.	0.	0.	0.	0.	2.5
53	Si Al Ca	0.	0.	26.	52.	0.	0.	0.	4.	11.	2.	4.	0.	0.	0.	0.	5.3
25	Si Ca Al	0.	0.	12.	48.	0.	0.	0.	2.	35.	0.	2.	0.	0.	0.	0.	2.4
3	Al Si Ca	0.	0.	39.	32.	0.	1.	0.	1.	17.	1.	10.	0.	0.	0.	0.	0.5
207	Si Al Fe	0.	0.	26.	60.	0.	0.	0.	9.	1.	0.	3.	0.	0.	0.	0.	17.6
8	Si Al Ti	0.	0.	22.	54.	0.	0.	0.	4.	6.	10.	4.	0.	0.	0.	0.	0.7
6	Fe Ca Si	0.	0.	5.	12.	0.	0.	0.	2.	22.	0.	59.	0.	0.	0.	0.	0.6
3	Si Fe Ca	0.	0.	0.	76.	0.	0.	0.	0.	6.	0.	18.	0.	0.	0.	0.	0.9
3	Ca Si Fe	0.	0.	10.	26.	0.	2.	0.	4.	36.	0.	21.	0.	0.	0.	0.	0.8
19	Si Na K	17.	0.	2.	66.	0.	0.	0.	8.	2.	3.	0.	0.	2.	0.	0.	2.0
8	Si Al Na	10.	0.	23.	54.	0.	0.	0.	6.	2.	1.	4.	0.	0.	0.	0.	0.6
11	Si Na Al	18.	0.	8.	63.	0.	0.	0.	3.	2.	3.	0.	0.	2.	0.	0.	1.0
7	Si Zn K	0.	0.	0.	74.	0.	0.	0.	9.	3.	3.	0.	0.	12.	0.	0.	0.5
1	Fe Si S	0.	0.	0.	19.	0.	16.	0.	0.	0.	0.	65.	0.	0.	0.	0.	0.8
12	Si Na Zn	14.	0.	3.	67.	0.	0.	0.	3.	1.	3.	0.	0.	8.	0.	0.	0.8

TABLE 4-30. - PSIT pure ash on filter Illinois #6. #if. 7% O₂.
0.2 g/min. 1500 K (Cont.)

122 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE 5.2

 1135 TOTALS - 1. 0. 18. 58. 0. 1. 0. 5. 5. 1. 11. 0. 1. 0. 0. 100.0

SAMPLE # 246 PSI PURE ASH on filter ILL#6, #if, 7%O₂, 0.2g/min, 2350F
 NUMBER 246 DISK 43 FILE 123 - 126 PARTICLES
 RUN 1 DATE 28-FEB-90 SUMMARY 126 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	17.1	7.	27.	28.	34.	4.	0.	0.
Si Al -	13.4	4.	15.	30.7	41.	10.	0.	0.
Si Al Fe	10.1	5.	13.	32.	43.	6.	0.	0.
Si Al Ca	5.3	1.	14.	45.	35.	5.	0.	0.
Si Al K	17.6	2.	10.	22.	52.	14.	1.	0.
OTHERS -	36.6	11.	17.	23.	41.	8.	0.	0.
TOTALS -	100.0	7.	17.	27.	42.	8.	0.	0.

Association for Information and Image Management
1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

3 of 6

TABLE 4-31. - PSIT/MIT-1 Illinois #6 1750 K. 7% O₂ total filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI/MIT-1 ILLINOIS #6 1750K, 7%O2, TOTAL FILTER SAMPLE
 NUMBER 5 DISK 29 FILE 117 - 120 PARTICLES
 RUN 1 DATE 2-APR-89 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.12173E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
117	Ca - -	0.	0.	0.	2.	0.	1.	0.	0.	97.	0.	0.	0.	0.	0.	0.	7.3
37	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	97.	0.	0.	0.	0.	2.5
94	Si - -	0.	0.	2.	94.	0.	0.	0.	1.	1.	0.	1.	0.	0.	0.	0.	9.1
142	Si Al -	0.	0.	31.	63.	0.	1.	0.	3.	1.	1.	2.	0.	0.	0.	0.	12.2
11	Al Si -	0.	0.	51.	48.	0.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	0.9
8	Fe Si -	0.	0.	1.	19.	0.	1.	0.	0.	1.	0.	78.	0.	0.	0.	0.	0.6
6	Ca Si -	0.	0.	2.	21.	0.	2.	0.	0.	76.	0.	0.	0.	0.	0.	0.	0.5
1	Fe S -	0.	0.	0.	0.	0.	24.	0.	0.	3.	0.	73.	0.	0.	0.	0.	0.5
262	Si Al K	0.	0.	25.	58.	0.	0.	0.	11.	1.	0.	4.	0.	0.	0.	0.	25.3
41	Si K Al	0.	0.	17.	52.	0.	0.	0.	20.	0.	0.	10.	0.	0.	0.	0.	4.2
38	Si Fe Al	0.	1.	15.	49.	0.	1.	0.	5.	2.	1.	26.	0.	0.	0.	0.	3.6
104	Si Al Fe	0.	0.	24.	53.	0.	1.	0.	6.	2.	1.	12.	0.	0.	0.	0.	8.3
17	Fe Si Al	0.	0.	11.	25.	0.	2.	0.	1.	1.	1.	60.	0.	0.	0.	0.	1.3
5	Al Si Fe	0.	1.	50.	35.	0.	0.	0.	2.	1.	1.	10.	0.	0.	0.	0.	0.9
7	Si Al Ti	0.	0.	26.	50.	0.	0.	0.	3.	5.	11.	4.	0.	0.	0.	0.	0.5
41	Si Al Ca	0.	0.	25.	56.	0.	1.	0.	3.	10.	2.	3.	0.	0.	0.	0.	3.3
23	Si Ca Al	0.	1.	11.	57.	0.	0.	0.	0.	31.	0.	0.	0.	0.	0.	0.	6.4
13	Si Fe K	0.	0.	10.	46.	0.	0.	0.	14.	1.	2.	27.	0.	0.	0.	0.	1.2
10	Si K Fe	0.	0.	14.	46.	0.	0.	0.	21.	0.	2.	16.	0.	1.	0.	0.	0.5
10	Fe Si K	0.	0.	7.	28.	0.	0.	0.	17.	0.	4.	44.	0.	0.	0.	0.	1.4
5	Si S Al	0.	0.	16.	48.	0.	22.	0.	9.	1.	0.	4.	0.	0.	0.	0.	0.5
22	Si Al S	0.	0.	26.	57.	0.	10.	0.	2.	1.	1.	2.	0.	1.	0.	0.	1.8
6	Fe Si Ca	0.	0.	8.	16.	0.	4.	0.	0.	12.	5.	55.	0.	0.	0.	0.	0.5
7	Si Al Na	11.	0.	25.	47.	0.	1.	0.	5.	4.	2.	5.	0.	0.	0.	0.	0.9
5	Si Na K	16.	0.	3.	64.	0.	0.	0.	7.	4.	2.	0.	0.	4.	0.	0.	0.5
88	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																4.9
1122	TOTALS -	0.	0.	18.	52.	0.	1.	0.	6.	11.	1.	10.	0.	0.	0.	0.	100.0

TABLE 4-31. - PSIT/MIT-1 Illinois #6 1750 K, 7% O₂, total filter (Cont.)

SAMPLE PSIT/MIT-1 ILLINOIS #6 1750K, 7%O2, TOTAL FILTER SAMPLE
 NUMBER 5 DISK 29 FILE 117 - 120 PARTICLES
 RUN 1 DATE 2-APR-89 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	7.3	7.	14.	17.	29.	31.	3.	0.
Si - -	9.1	2.	20.	25.	45.	7.	1.	0.
Si AL -	12.2	1.	13.	28.	38.	17.	4.	0.
Si AL K	25.3	2.	6.	10.	47.	26.	8.	0.
Si K AL	4.2	0.	6.	5.	36.	28.	25.	0.
Si AL Fe	0.3	3.	10.	22.	34.	27.	4.	0.
Si Ca AL	6.4	0.	1.	5.	91.	2.	0.	0.
OTHERS -	27.2	4.	17.	18.	37.	18.	7.	0.
TOTALS -	100.0	3.	12.	17.	43.	20.	6.	0.

TABLE 4-32. - Arizona ash on filter, Illinois #6, 21IM1a, impactor #1

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 275 PSI/ARIZONA ASH on filter, Ill. #6, 21IM1a, impactor #1
 NUMBER 275 DISK 44 FILE 125 - 128 PARTICLES
 RUN 1 DATE 2-MAR-90 SUMMARY 128 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.14634E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
184	Si - -	0.	0.	2.	94.	0.	0.	0.	2.	1.	0.	1.	0.	0.	0.	0.	17.6
44	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	98.	0.	0.	0.	0.	3.6
24	Ca - -	0.	0.	0.	3.	0.	3.	6.	0.	86.	0.	1.	0.	1.	0.	0.	1.2
11	Fe Si -	0.	0.	2.	24.	0.	1.	0.	0.	1.	0.	72.	0.	0.	0.	0.	0.7
100	Si Al -	0.	0.	29.	63.	0.	0.	0.	4.	2.	1.	2.	0.	0.	0.	0.	10.3
14	Al Si -	0.	0.	51.	44.	0.	0.	0.	4.	0.	0.	0.	0.	0.	0.	0.	1.6
10	Ca Cl -	0.	0.	0.	2.	0.	3.	13.	0.	81.	0.	1.	0.	0.	0.	0.	0.7
22	Ca S -	0.	0.	0.	2.	0.	28.	0.	0.	69.	0.	0.	0.	0.	0.	0.	1.5
259	Si Al K	1.	0.	25.	60.	0.	0.	0.	8.	2.	1.	4.	0.	0.	0.	0.	25.5
5	Si S Al	0.	0.	17.	34.	0.	21.	0.	3.	15.	7.	3.	0.	0.	0.	0.	0.6
134	Si Al Fe	0.	0.	24.	54.	0.	0.	0.	6.	4.	1.	11.	0.	0.	0.	0.	10.1
20	Si Fe Al	0.	0.	16.	46.	0.	1.	0.	5.	4.	2.	25.	0.	0.	0.	0.	2.0
25	Fe Si Al	0.	0.	10.	30.	0.	0.	0.	4.	3.	1.	52.	0.	0.	0.	0.	2.1
16	Si Al Ti	0.	0.	24.	47.	0.	2.	0.	5.	7.	11.	4.	0.	0.	0.	0.	1.3
5	Si Ca Fe	0.	0.	9.	48.	0.	4.	0.	5.	17.	3.	12.	0.	0.	0.	0.	0.5
8	Ca Si Fe	0.	0.	8.	25.	0.	1.	0.	1.	48.	0.	16.	0.	0.	0.	0.	0.6
6	Fe Si Ca	0.	0.	3.	20.	0.	3.	0.	6.	16.	0.	52.	0.	0.	0.	0.	0.5
20	Si Ca Al	0.	0.	15.	48.	0.	2.	1.	6.	22.	0.	6.	0.	0.	0.	0.	1.1
94	Si Al Ca	0.	0.	26.	50.	0.	2.	0.	5.	11.	1.	5.	0.	0.	0.	0.	7.8
20	Ca Si Al	0.	0.	13.	29.	0.	4.	1.	1.	50.	0.	1.	0.	0.	0.	0.	1.8
13	Ca Cl S	0.	0.	0.	1.	0.	9.	13.	0.	77.	0.	0.	0.	0.	0.	0.	0.6
11	Si Fe K	0.	0.	9.	43.	0.	2.	0.	13.	5.	3.	25.	0.	0.	0.	0.	0.8
11	Ca S Si	0.	0.	8.	16.	0.	21.	2.	0.	45.	2.	4.	1.	1.	0.	0.	1.4
112	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.0
1168	TOTALS -	0.	0.	18.	55.	0.	2.	0.	5.	9.	1.	10.	0.	0.	0.	0.	100.0

TABLE 4-32. - Arizona ash on filter, Illinois #6, 21IM1a, impactor #1 (Cont.)

SAMPLE # 275 PSI/ARIZONA ASH on filter, Ill. #6, 21IM1a, impactor #1
 NUMBER 275 DISK 44 FILE 125 - 128 PARTICLES
 RUN 1 DATE 2-MAR-90 SUMMARY 128 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	17.6	2.	7.	24.	51.	16.	0.	0.
Si AL -	10.3	2.	22.	20.	41.	14.	1.	0.
Si AL K	25.5	3.	9.	20.	53.	14.	1.	0.
Si AL Fe	10.1	10.	24.	15.	40.	10.	1.	0.
Si AL Ca	7.8	8.	35.	19.	32.	6.	0.	0.
OTHERS -	28.6	7.	16.	27.	32.	18.	0.	0.
TOTALS -	100.0	5.	16.	22.	43.	14.	0.	0.

**TABLE 4-33. - PSIT #88 San Miguel Lignite DTF ash, 7% O₂, 1500 K,
3.0s RST varied**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI #88 SAN MIGUEL LIGNITE DTF ASH 7%O₂, 2350F, 3.0sec RST VARIED.

NUMBER 83 DISK 44 FILE 105 - 108 PARTICLES
RUN 1 DATE 20-NOV-89 SUMMARY 108 TOTAL 1156
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.10408E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
87	Si - -	0.	0.	5.	91.	0.	0.	0.	2.	2.	0.	0.	0.	0.	0.	0.	10.5
277	Si Al -	0.	0.	24.	74.	0.	0.	0.	1.	1.	0.	0.	0.	0.	0.	0.	33.3
6	Fe Si -	0.	0.	3.	16.	0.	0.	0.	0.	2.	0.	79.	0.	0.	0.	0.	0.5
13	Si Ca -	0.	0.	0.	82.	0.	0.	0.	0.	17.	0.	0.	0.	0.	0.	0.	1.5
283	Si Al Ca	0.	0.	21.	66.	0.	0.	0.	1.	10.	1.	0.	0.	0.	0.	0.	28.5
95	Si Ca Al	0.	0.	15.	61.	0.	0.	0.	1.	21.	1.	0.	0.	0.	0.	0.	8.0
9	Ca Si Al	0.	0.	12.	34.	0.	0.	2.	0.	48.	2.	1.	0.	0.	0.	0.	0.6
103	Si Al K	0.	0.	16.	73.	0.	0.	0.	8.	1.	1.	0.	0.	0.	0.	0.	9.4
29	Si K Al	0.	0.	11.	73.	0.	0.	0.	16.	0.	0.	0.	0.	0.	0.	0.	2.5
37	Si Al Ti	0.	0.	24.	65.	0.	0.	0.	0.	3.	8.	0.	0.	0.	0.	0.	2.7
32	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																2.6
972	TOTALS -	0.	0.	18.	71.	0.	0.	0.	2.	7.	1.	1.	0.	0.	0.	0.	100.0

SAMPLE PSI #88 SAN MIGUEL LIGNITE DTF ASH 7%O₂, 2350F, 3.0sec RST VARIED.

NUMBER 88 DISK 44 FILE 105 - 108 PARTICLES
RUN 1 DATE 20-NOV-89 SUMMARY 108 TOTAL 1156
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	10.5	0.	8.	15.	58.	19.	0.	0.
Si Al -	33.3	0.	6.	13.	58.	21.	1.	0.
Si Al Ca	28.5	1.	12.	18.	46.	22.	1.	0.
Si Ca Al	8.0	2.	21.	17.	33.	22.	6.	0.
Si Al K	9.4	1.	7.	27.	37.	27.	1.	0.
OTHERS -	10.4	1.	19.	24.	29.	25.	2.	0.
TOTALS -	100.0	1.	10.	18.	47.	22.	2.	0.

TABLE 4-34. - PSIT #89 San Miguel Lignite DTF ash 21% O₂, 1500 K, 3.0s RST

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE PSI #89 SAN MIGUEL LIGNITE DTF ASH 21%O2 2350F 3 sec. RST

NUMBER 4 DISK 32 FILE 113 - 116 PARTICLES

RUN 1 DATE 23-JUN-89 SUMMARY 116 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.12524E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
125	Si - -	1.	0.	6.	87.	0.	0.	0.	3.	3.	0.	0.	0.	0.	0.	0.	11.6
248	Si Al -	1.	0.	23.	71.	0.	0.	0.	2.	3.	1.	0.	0.	0.	0.	0.	23.6
11	Si Ca -	0.	0.	1.	83.	0.	0.	0.	0.	16.	0.	0.	0.	0.	0.	0.	1.1
4	Ca S -	0.	0.	0.	0.	0.	45.	0.	0.	55.	0.	0.	0.	0.	0.	0.	0.7
388	Si Al Ca	1.	0.	22.	64.	0.	0.	0.	1.	10.	1.	0.	0.	0.	0.	0.	28.9
112	Si Ca Al	0.	0.	14.	61.	0.	0.	0.	1.	20.	2.	1.	0.	0.	0.	0.	10.0
14	Ca Si Al	0.	0.	16.	32.	0.	0.	1.	0.	48.	2.	0.	0.	0.	0.	0.	0.9
124	Si Al K	1.	0.	13.	75.	0.	0.	0.	8.	3.	0.	0.	0.	0.	0.	0.	10.9
28	Si K Al	0.	0.	12.	65.	0.	0.	0.	19.	2.	1.	0.	0.	0.	0.	0.	3.8
24	Si Al Na	10.	0.	18.	66.	0.	0.	0.	1.	4.	1.	0.	0.	0.	0.	0.	1.8
1	Si Ti Ca	0.	0.	9.	46.	0.	0.	0.	0.	19.	24.	0.	0.	0.	0.	0.	0.5
8	Si Al Ti	0.	0.	23.	57.	0.	0.	0.	3.	8.	10.	0.	0.	0.	0.	0.	0.5
92	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.9
1179	TOTALS -	1.	0.	17.	67.	0.	1.	0.	3.	9.	1.	1.	0.	0.	0.	0.	100.0

SAMPLE PSI #89 SAN MIGUEL LIGNITE DTF ASH 21%O2 2350F 3 sec. RST

NUMBER 4 DISK 32 FILE 113 - 116 PARTICLES

RUN 1 DATE 23-JUN-89 SUMMARY 116 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	11.6	5.	13.	12.	51.	17.	2.	0.
Si Al -	23.6	3.	12.	16.	51.	19.	0.	0.
Si Al Ca	28.9	6.	20.	23.	34.	16.	1.	0.
Si Ca Al	10.0	3.	11.	20.	44.	19.	2.	0.
Si Al K	10.9	2.	8.	17.	41.	31.	1.	0.
OTHERS -	15.0	5.	15.	18.	48.	12.	2.	0.
TOTALS -	100.0	4.	14.	18.	44.	18.	1.	0.

TABLE 4-35. - Arizona Illinois #6 ash on filter 1.4 kg/h.
1304°C. impactor #1 + cup

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 552 PSI/ARIZONA ILLINOIS#6 ash on filter 1.4kg/hr, 1304C, Imp. #1+cup
 NUMBER 552 DISK 54 FILE 101 - 104 PARTICLES
 RUN 1 DATE 23-OCT-91 SUMMARY 104 TOTAL 1068
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.12714E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
128	Si - -	0.	0.	2.	93.	0.	1.	0.	2.	1.	0.	1.	0.	0.	0.	0.	12.0
39	Fe - -	0.	0.	0.	3.	0.	0.	0.	0.	1.	1.	94.	0.	0.	0.	0.	3.3
79	Si Al -	0.	0.	31.	61.	0.	1.	0.	3.	1.	0.	2.	0.	0.	0.	0.	7.2
16	Al Si -	0.	0.	52.	47.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	2.4
22	Ca S -	0.	0.	0.	1.	0.	43.	0.	0.	55.	0.	0.	0.	0.	0.	0.	1.8
7	Fe Si -	0.	0.	2.	26.	0.	0.	0.	1.	0.	0.	71.	0.	0.	0.	0.	0.7
24	Si S Al	0.	0.	17.	45.	0.	28.	0.	2.	2.	1.	4.	0.	1.	0.	0.	2.4
63	Si Al S	0.	0.	27.	51.	0.	12.	0.	3.	2.	0.	4.	0.	0.	0.	0.	5.3
11	S Si Al	0.	0.	15.	31.	0.	47.	0.	2.	1.	2.	1.	0.	1.	0.	0.	0.9
2	Al Si S	0.	0.	58.	35.	0.	8.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.5
208	Si Al K	0.	0.	28.	57.	0.	1.	0.	8.	1.	1.	3.	0.	0.	0.	0.	19.7
7	Si S Ca	0.	0.	9.	43.	0.	21.	5.	5.	12.	0.	2.	0.	1.	0.	0.	0.8
16	Ca S Si	0.	0.	4.	14.	0.	26.	0.	0.	52.	0.	2.	0.	0.	0.	0.	1.0
12	Ca Si S	0.	0.	5.	20.	0.	14.	0.	0.	51.	4.	6.	0.	0.	0.	0.	1.4
149	Si Al Fe	0.	0.	26.	51.	0.	2.	0.	5.	3.	1.	11.	0.	0.	0.	0.	14.7
27	Si Fe Al	0.	0.	17.	46.	0.	3.	0.	5.	3.	1.	24.	0.	0.	0.	0.	1.9
25	Fe Si Al	0.	0.	12.	21.	0.	3.	0.	1.	5.	0.	57.	0.	0.	0.	0.	2.4
7	Ca S Fe	0.	0.	4.	5.	0.	33.	0.	0.	46.	0.	11.	1.	0.	0.	0.	0.7
6	Si Al Ti	0.	0.	23.	50.	0.	3.	0.	4.	5.	9.	6.	0.	0.	0.	0.	0.6
8	Ca Si Al	0.	0.	16.	29.	0.	1.	0.	0.	43.	1.	10.	0.	0.	0.	0.	0.6
50	Si Al Ca	0.	0.	24.	49.	0.	5.	0.	3.	12.	1.	5.	1.	0.	0.	0.	5.4
13	Si Ca Al	0.	0.	19.	40.	0.	3.	0.	2.	26.	0.	10.	0.	0.	0.	0.	1.5
3	Al Si Ca	0.	0.	49.	34.	2.	0.	2.	2.	9.	1.	1.	0.	0.	0.	0.	0.5
7	Si Al Na	13.	0.	22.	50.	0.	1.	0.	6.	0.	0.	7.	0.	0.	0.	0.	0.7
8	OTHERS -	0.	7.	9.	10.	0.	8.	0.	0.	38.	3.	24.	0.	2.	0.	0.	0.9
130	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																10.4
1068	TOTALS -	0.	0.	19.	49.	0.	7.	0.	4.	8.	1.	10.	0.	0.	0.	0.	100.0

TABLE 4-35. - Arizona Illinois #6 ash on filter 1.4 kg/h.
1304°C, impactor #1 + cup (Cont.)

SAMPLE # 552 PSI/ARIZONA ILLINOIS#6 ash on filter 1.4kg/hr, 1304C, Imp. #1+cup
 NUMBER 552 DISK 54 FILE 101 - 104 PARTICLES
 RUN 1 DATE 23-OCT 91 SUMMARY 104 TOTAL 1068
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	12.0	1.	28.	41.	21.	9.	0.	0.
Si Al -	7.2	2.	21.	42.	28.	6.	2.	0.
Si Al K	19.7	4.	29.	28.	23.	12.	3.	0.
Si Al S	5.3	9.	27.	24.	23.	12.	4.	0.
Si Al Fe	14.7	11.	45.	28.	12.	4.	0.	0.
Si Al Ca	5.4	6.	41.	28.	23.	2.	0.	0.
OTHERS -	35.6	7.	29.	27.	23.	12.	2.	0.
TOTALS -	100.0	6.	31.	30.	22.	10.	2.	0.

**TABLE 4-36. - Arizona Illinois #6 impactors 2+3+4, 1 kg/h,
1304°C, 11 port**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 553 PSI/ARIZONA ILLINOIS#6 Imp.2+3+4, 1.4 kg/hr, 1304C, 11 port
 NUMBER 553 DISK 41 FILE 121 - 124 PARTICLES
 RUN 1 DATE 17-DEC-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.11255E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
85	Si - -	0.	0.	1.	92.	0.	1.	0.	2.	1.	0.	2.	0.	0.	0.	0.	7.7
29	S - -	0.	0.	3.	2.	0.	90.	0.	0.	1.	1.	1.	1.	0.	0.	0.	2.5
19	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	97.	0.	0.	0.	0.	2.2
72	Ca S -	0.	0.	1.	2.	0.	43.	0.	0.	52.	0.	1.	0.	0.	0.	0.	2.4
68	Si Al -	0.	0.	38.	53.	0.	2.	0.	4.	1.	1.	2.	0.	0.	0.	0.	5.8
41	Si S Al	0.	0.	21.	41.	0.	26.	0.	1.	2.	5.	3.	0.	1.	0.	0.	1.8
101	Si Al S	0.	0.	31.	45.	0.	16.	0.	1.	1.	1.	3.	0.	0.	0.	0.	9.7
29	S Si Al	0.	0.	16.	22.	0.	57.	0.	0.	2.	0.	2.	1.	0.	0.	0.	3.1
9	S Al Si	0.	0.	28.	23.	0.	45.	0.	2.	1.	2.	0.	0.	0.	0.	0.	0.8
3	Al Si S	0.	0.	42.	40.	0.	15.	0.	0.	2.	0.	0.	0.	0.	0.	0.	0.5
3	Fe Al Ca	0.	0.	18.	12.	0.	8.	0.	0.	13.	3.	44.	0.	2.	0.	0.	0.7
9	Si Ca S	0.	0.	19.	35.	0.	20.	0.	5.	20.	0.	0.	0.	0.	0.	0.	1.1
70	Ca S Si	0.	0.	6.	11.	0.	35.	0.	0.	43.	2.	1.	0.	0.	0.	0.	2.1
6	Si S Ca	0.	0.	5.	49.	0.	32.	0.	1.	12.	0.	1.	0.	0.	0.	0.	0.6
176	Si Al K	0.	0.	29.	56.	0.	2.	0.	9.	0.	0.	3.	0.	0.	0.	0.	15.6
18	Si Fe Al	0.	0.	19.	47.	0.	3.	0.	4.	4.	1.	22.	0.	0.	0.	0.	2.4
139	Si Al Fe	1.	0.	27.	49.	0.	4.	0.	6.	2.	1.	10.	0.	0.	0.	0.	22.2
11	Fe Si Al	0.	0.	15.	30.	0.	3.	0.	3.	4.	1.	42.	0.	2.	0.	0.	0.7
47	Si Al Ca	0.	0.	25.	45.	0.	5.	0.	3.	12.	2.	7.	1.	0.	0.	0.	3.9
10	Si Ca Al	0.	0.	14.	44.	0.	5.	0.	2.	27.	1.	7.	0.	0.	0.	0.	1.0
6	Ca Si Al	0.	0.	15.	27.	1.	3.	0.	0.	47.	0.	7.	0.	0.	0.	0.	0.6
4	Al Si Ca	0.	0.	36.	29.	0.	2.	0.	0.	15.	4.	14.	0.	0.	0.	0.	0.7
16	Si Al Na	11.	0.	23.	52.	0.	2.	0.	6.	0.	1.	5.	0.	0.	0.	0.	1.6
6	Si Al Ti	0.	0.	26.	48.	0.	2.	0.	5.	6.	8.	4.	0.	1.	0.	0.	0.5
20	Ca S Fe	0.	0.	0.	3.	4.	23.	0.	0.	58.	0.	10.	0.	0.	0.	0.	1.3
5	S Si Ti	0.	0.	0.	11.	0.	80.	0.	0.	0.	8.	0.	0.	0.	0.	0.	0.5
1	S Al Zn	0.	0.	13.	11.	0.	43.	0.	11.	0.	11.	0.	0.	11.	0.	0.	0.5
7	OTHERS -	0.	0.	9.	14.	0.	6.	0.	3.	6.	47.	16.	0.	0.	0.	0.	1.1

119 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE 6.0

TABLE 4-36. - Arizona Illinois #6 impactors 2+3+4, 1 kg/h.
1304°C, 11 port (Cont.)

1129 TOTALS - 1. 0. 21. 43. 0. 13. 0. 4. 7. 2. 8. 0. 0. 0. 0. 100.0

SAMPLE # 553 PSI/ARIZONA ILLINOIS#6 Imp.2+3+4, 1.4 kg/hr, 1304C, 11 port
 NUMBER 553 DISK 41 FILE 121 - 124 PARTICLES
 RUN 1 DATE 17-DEC-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>5000 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	7.7	27.	59.	10.	3.	0.	0.	0.
Si AL -	5.8	68.	20.	11.	0.	0.	0.	0.
Si AL S	9.7	43.	47.	10.	0.	0.	0.	0.
Si AL K	15.6	43.	44.	11.	1.	0.	0.	0.
Si AL Fe	22.2	46.	51.	3.	1.	0.	0.	0.
OTHERS -	38.9	56.	25.	16.	4.	0.	0.	0.
TOTALS -	100.0	49.	38.	11.	2.	0.	0.	0.

**TABLE 4-37. - Arizona Illinois #6 ash on filter 1.4 kg/h.
1304°C. impactors 5+6+7+8+AF**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 554 PSI/ARIZONA ILL#6 ASH ON FILTER 1.4KG/HR, 1304C, IMPS 5+6+7+8+AF
 NUMBER 554 DISK 47 FILE 120 - 123 PARTICLES
 RUN 1 DATE 16-MAR-92 SUMMARY 123 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.53992E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
29	S - -	0.	0.	3.	2.	0.	88.	0.	0.	3.	1.	1.	0.	0.	0.	0.	3.9
79	Si - -	0.	0.	3.	91.	0.	1.	0.	2.	1.	0.	2.	0.	0.	0.	0.	6.3
7	Ca - -	0.	1.	0.	2.	1.	4.	0.	0.	90.	0.	1.	1.	0.	0.	0.	0.7
42	Fe - -	0.	0.	2.	3.	0.	1.	0.	0.	2.	1.	91.	0.	0.	0.	0.	3.1
11	S Ca -	0.	0.	0.	0.	0.	71.	0.	0.	27.	1.	0.	0.	0.	0.	0.	0.8
57	Ca S -	0.	0.	1.	1.	0.	46.	0.	0.	51.	0.	0.	0.	0.	0.	0.	1.8
42	Si Al -	0.	0.	39.	54.	0.	1.	0.	4.	0.	0.	2.	0.	0.	0.	0.	4.0
4	Fe S -	0.	0.	0.	1.	0.	26.	0.	0.	0.	0.	73.	0.	0.	0.	0.	0.5
24	S Si Al	1.	0.	19.	29.	0.	44.	1.	1.	2.	1.	2.	1.	0.	0.	0.	3.3
21	Si S Al	0.	0.	22.	43.	0.	29.	1.	1.	1.	1.	2.	1.	0.	0.	0.	2.8
45	Si Al S	0.	0.	28.	45.	0.	16.	0.	3.	2.	1.	4.	0.	0.	0.	0.	5.7
11	Si Ca Al	3.	0.	17.	44.	0.	1.	0.	2.	25.	0.	8.	0.	0.	0.	0.	2.1
13	Ca Si Al	0.	0.	15.	21.	3.	2.	0.	0.	48.	2.	6.	0.	0.	0.	0.	1.7
30	Si Al Ca	0.	0.	26.	49.	0.	2.	0.	4.	11.	2.	5.	0.	0.	0.	0.	2.4
4	Ca Si Fe	0.	0.	7.	19.	3.	2.	1.	2.	56.	1.	9.	0.	0.	0.	0.	0.6
180	Si Al K	1.	0.	31.	55.	0.	1.	0.	8.	0.	0.	4.	0.	0.	0.	0.	17.4
35	Ca S Si	0.	0.	4.	12.	0.	36.	0.	1.	43.	1.	3.	0.	0.	0.	0.	1.2
6	S Ca Si	0.	0.	11.	14.	0.	45.	0.	0.	28.	0.	1.	0.	0.	0.	0.	0.7
228	Si Al Fe	1.	0.	28.	49.	0.	2.	0.	6.	2.	1.	11.	0.	0.	0.	0.	19.2
24	Fe Si Al	0.	0.	14.	23.	0.	3.	0.	1.	3.	3.	53.	0.	0.	0.	0.	1.9
13	Si Fe Al	2.	0.	20.	41.	0.	3.	0.	4.	3.	1.	27.	0.	0.	0.	0.	2.0
22	Si Al Na	10.	0.	27.	49.	0.	1.	0.	7.	1.	1.	5.	0.	0.	0.	0.	1.8
7	Ca S Fe	2.	0.	5.	2.	3.	26.	0.	1.	44.	0.	17.	0.	0.	0.	0.	0.8
11	Si Al Ti	0.	0.	29.	47.	0.	2.	0.	2.	4.	11.	4.	0.	0.	0.	0.	0.7
4	Si Ti Al	0.	0.	18.	35.	0.	9.	0.	0.	6.	21.	10.	0.	0.	0.	0.	0.7
1	S Ti Cu	0.	0.	0.	0.	0.	65.	0.	0.	0.	20.	0.	14.	0.	0.	0.	0.5
3	Si Al Cl	0.	0.	26.	56.	0.	7.	11.	0.	0.	0.	0.	0.	0.	0.	0.	0.6
45	OTHERS -	1.	1.	10.	13.	2.	14.	3.	4.	13.	8.	30.	0.	0.	0.	0.	4.2
120	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.0

**TABLE 4-37. - Arizona Illinois #6 ash on filter 1.4 kg/h.
1304°C. impactors 5+6+7+8+AF (Cont.)**

1118 TOTALS - 1. 0. 20. 40. 0. 13. 1. 4. 8. 1. 11. 0. 0. 0. 0. 100.0

SAMPLE 554 PSI/ARIZONA ILL#6 ASH ON FILTER 1.4KG/HR, 1304C, IMPS 5+6+7+8+AF
NUMBER 554 DISK 47 FILE 120 - 123 PARTICLES
RUN 1 DATE 16-MAR-92 SUMMARY 123 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	6.3	53.	30.	13.	2.	2.	0.	0.
Si AL -	4.0	33.	50.	10.	6.	0.	0.	0.
Si AL K	17.4	48.	39.	10.	2.	1.	0.	0.
Si AL S	5.7	23.	63.	8.	4.	2.	0.	0.
Si AL Fe	19.2	67.	28.	4.	0.	0.	0.	0.
OTHERS -	4.2	57.	43.	0.	0.	0.	0.	0.
OTHERS -	43.1	45.	25.	12.	10.	7.	1.	0.
TOTALS -	100.0	49.	32.	9.	5.	3.	0.	0.

**TABLE 4-38. - Arizona Illinois #6 ash 1304°C. 1.4 kg/h.
port 5. impactors #1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 555 PSI/UA 47D ILL #6 ASH 1304C 1.4KG/HR PORT 5 IMP # 1+CUP
NUMBER 555 DISK 52 FILE 125 - 128 PARTICLES
RUN 1 DATE 24-APR-92 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.48205E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
8	Al - -	0.	0.	95.	0.	1.	1.	1.	0.	1.	0.	2.	0.	0.	0.	0.	0.8
33	S - -	0.	0.	2.	2.	0.	89.	0.	2.	2.	0.	1.	1.	0.	0.	0.	4.5
29	Si - -	0.	0.	1.	88.	0.	4.	0.	3.	1.	0.	1.	0.	0.	0.	0.	3.4
18	S Al -	0.	0.	17.	2.	0.	78.	0.	0.	1.	0.	1.	0.	0.	0.	0.	2.7
40	S Si -	0.	0.	0.	27.	0.	71.	0.	1.	0.	1.	0.	0.	0.	0.	0.	5.4
28	Si S -	0.	0.	0.	72.	0.	24.	0.	2.	1.	0.	1.	0.	0.	0.	0.	4.9
20	S Ca -	0.	0.	0.	1.	0.	71.	0.	0.	28.	0.	0.	0.	0.	0.	0.	3.1
12	S Al Si	0.	0.	16.	12.	0.	65.	0.	0.	2.	0.	3.	1.	2.	0.	0.	1.7
27	S Si Al	0.	0.	13.	26.	0.	54.	0.	2.	3.	1.	1.	0.	0.	0.	0.	1.5
25	Si S Al	0.	0.	13.	56.	0.	24.	0.	2.	2.	1.	2.	0.	0.	0.	0.	1.1
22	Si Al S	0.	0.	25.	51.	0.	13.	0.	6.	2.	1.	1.	0.	1.	0.	0.	3.0
21	S Fe K	2.	0.	0.	0.	0.	59.	0.	13.	0.	0.	25.	0.	0.	0.	0.	1.6
7	S Fe Si	0.	0.	2.	12.	0.	61.	0.	2.	4.	0.	18.	0.	2.	0.	0.	0.7
55	S Si Fe	0.	0.	0.	24.	0.	60.	0.	1.	2.	2.	10.	0.	0.	0.	0.	4.7
17	Si S Fe	0.	0.	0.	53.	0.	31.	0.	2.	2.	2.	9.	0.	0.	0.	0.	1.6
126	S Ca Si	0.	0.	1.	14.	0.	53.	0.	2.	27.	2.	1.	0.	0.	0.	0.	12.8
195	S Si Ca	0.	0.	1.	24.	0.	55.	0.	2.	13.	1.	3.	0.	0.	0.	0.	12.7
48	Si S Ca	0.	0.	1.	48.	0.	30.	0.	3.	16.	0.	1.	0.	0.	0.	0.	5.4
9	S Si Na	14.	0.	3.	21.	0.	50.	0.	2.	6.	1.	3.	0.	0.	0.	0.	0.5
21	S Si Ti	0.	0.	0.	25.	0.	53.	0.	1.	4.	11.	3.	0.	2.	0.	0.	1.0
6	S Ti Si	0.	0.	0.	10.	0.	69.	0.	0.	3.	11.	4.	0.	2.	0.	0.	0.5
12	Si S Ti	0.	0.	2.	48.	0.	28.	0.	2.	0.	14.	0.	0.	6.	0.	0.	2.8
9	S Ca Fe	0.	0.	0.	9.	6.	50.	0.	9.	15.	0.	11.	0.	0.	0.	0.	0.9
7	S Ca Ti	0.	0.	0.	10.	0.	46.	0.	6.	25.	12.	0.	0.	0.	0.	0.	0.8
2	S Ti Ca	0.	0.	0.	13.	0.	54.	0.	0.	16.	16.	0.	0.	0.	0.	0.	0.5
34	S Si K	0.	0.	0.	24.	0.	62.	0.	11.	1.	1.	1.	0.	0.	0.	0.	3.7
20	Si S K	0.	0.	0.	58.	0.	28.	0.	11.	0.	1.	3.	0.	0.	0.	0.	3.2
4	S Si Mg	0.	14.	8.	21.	0.	41.	0.	7.	3.	0.	6.	0.	0.	0.	0.	0.5
5	S Si Zn	0.	0.	0.	32.	0.	47.	0.	1.	2.	5.	2.	0.	10.	0.	0.	0.6
6	S Ca K	0.	0.	0.	4.	0.	54.	0.	12.	29.	0.	0.	0.	0.	0.	0.	0.7

**TABLE 4-38. - Arizona Illinois #6 ash 1304°C, 1.4 kg/h,
port 5, impactors #1 + cup (Cont.)**

6	Si Al K	0.	0.	27.	59.	0.	3.	0.	8.	1.	1.	2.	0.	0.	0.	0.	1.3
11	OTHERS	0.	0.	5.	19.	0.	29.	0.	3.	11.	3.	31.	0.	0.	0.	0.	1.7
119	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.9
1002	TOTALS -	1.	0.	4.	29.	0.	46.	1.	3.	10.	2.	3.	0.	1.	0.	0.	100.0

SAMPLE 555 PSI/UA 47D ILL #6 ASH 1304C 1.4KG/HR PORT 5 IMP # 1+CUP
NUMBER 555 DISK 52 FILE 125 - 128 PARTICLES
RUN 1 DATE 24-APR-92 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PY. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S - -	4.5	58.	37.	3.	2.	0.	0.	0.
S Si -	5.4	38.	49.	8.	5.	0.	0.	0.
Si S -	4.9	21.	73.	6.	0.	0.	0.	0.
S Si Fe	4.7	26.	43.	22.	7.	1.	0.	0.
S Ca Si	12.8	19.	48.	18.	14.	1.	0.	0.
S Si Ca	12.7	18.	35.	33.	13.	1.	0.	0.
Si S Ca	5.4	19.	60.	19.	2.	0.	0.	0.
OTHERS -	49.6	32.	33.	13.	15.	7.	1.	0.
TOTALS -	100.0	28.	40.	16.	12.	4.	0.	0.

TABLE 4-39. - Arizona 47D Illinois #6 ash 1304°C, 1.4 kg/h.
impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 556 PSI/UA 47D ILL#6 ASH 1304C 1.4 KG/HR IMP 2+3+4
NUMBER 556 DISK 52 FILE 129 - 132 PARTICLES
RUN 1 DATE 26-APR-92 SUMMARY 132 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500J 0

TOTAL Volume FACTOR: 0.90056E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
12	S - -	0.	0.	1.	3.	0.	90.	0.	1.	3.	0.	1.	0.	1.	0.	0.	1.2
111	Si - -	0.	0.	2.	94.	0.	1.	0.	2.	1.	0.	1.	0.	0.	0.	0.	10.3
40	Fe - -	0.	0.	1.	3.	0.	2.	0.	0.	1.	1.	93.	0.	0.	0.	0.	4.0
31	Ca - -	0.	0.	0.	0.	0.	5.	0.	0.	93.	0.	1.	0.	0.	0.	0.	2.2
46	Si Al -	0.	0.	26.	67.	0.	1.	0.	3.	1.	0.	2.	0.	0.	0.	0.	4.1
8	S Ca -	0.	0.	0.	0.	0.	66.	0.	0.	34.	0.	0.	0.	0.	0.	0.	0.7
29	Ca S -	0.	0.	0.	1.	0.	32.	0.	0.	65.	0.	1.	0.	0.	0.	0.	1.7
5	Fe S -	0.	0.	0.	1.	0.	25.	0.	0.	0.	0.	73.	0.	0.	0.	0.	0.8
178	Si Al K	0.	0.	27.	57.	0.	1.	0.	9.	1.	0.	4.	0.	0.	0.	0.	15.2
16	Si S Ca	0.	1.	10.	41.	0.	26.	1.	2.	15.	1.	3.	1.	0.	0.	0.	1.5
6	Ca Si S	0.	0.	9.	24.	0.	21.	0.	3.	36.	0.	6.	0.	0.	0.	0.	0.7
15	Ca S Si	0.	0.	7.	17.	0.	27.	0.	1.	45.	1.	3.	0.	0.	0.	0.	1.0
15	S Si Ca	0.	0.	7.	24.	0.	44.	0.	2.	18.	1.	1.	0.	0.	0.	0.	1.5
9	Si Ca S	0.	0.	11.	38.	1.	16.	0.	3.	24.	2.	5.	0.	0.	0.	0.	1.1
13	S Ca Si	0.	0.	7.	15.	0.	50.	1.	1.	22.	1.	1.	0.	1.	0.	0.	1.3
46	Si S Al	0.	0.	17.	44.	0.	26.	1.	3.	5.	0.	4.	0.	0.	0.	0.	5.9
25	S Si Al	0.	0.	17.	29.	0.	41.	1.	2.	6.	1.	3.	0.	1.	0.	0.	3.1
60	Si Al S	0.	0.	24.	50.	0.	13.	0.	3.	3.	1.	4.	0.	0.	0.	0.	6.0
6	Fe Si Ca	0.	0.	7.	21.	0.	1.	0.	0.	12.	1.	58.	0.	0.	0.	0.	0.6
27	Si Fe Al	0.	0.	16.	48.	0.	2.	0.	4.	5.	1.	23.	0.	0.	0.	0.	2.7
22	Fe Si Al	0.	1.	13.	27.	0.	2.	0.	1.	3.	1.	51.	0.	0.	0.	0.	1.7
149	Si Al Fe	0.	0.	26.	50.	0.	2.	0.	5.	4.	1.	11.	0.	0.	0.	0.	11.0
57	Si Al Ca	0.	0.	25.	48.	0.	3.	0.	3.	13.	2.	5.	0.	0.	0.	0.	4.9
17	Si Ca Al	0.	0.	14.	50.	0.	5.	0.	1.	24.	0.	5.	0.	0.	0.	0.	1.4
0	Ca Si Al	0.	0.	16.	27.	0.	3.	0.	2.	45.	1.	7.	1.	0.	0.	0.	0.6
12	Ca S Fe	0.	0.	2.	4.	0.	31.	0.	0.	50.	1.	11.	0.	0.	0.	0.	0.7
1	S Fe Ca	0.	0.	0.	9.	0.	65.	0.	0.	12.	0.	14.	0.	0.	0.	0.	0.5
12	Si Al Ti	0.	0.	22.	49.	0.	1.	0.	7.	4.	12.	5.	0.	0.	0.	0.	1.3
15	Si Al Na	9.	0.	29.	47.	0.	2.	0.	6.	3.	0.	4.	0.	0.	0.	0.	1.6
129	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																10.4
1120	TOTALS -	0.	0.	16.	44.	0.	13.	0.	4.	10.	1.	11.	0.	0.	0.	0.	100.0

TABLE 4-39. - Arizona 47D Illinois #6 ash 1304°C, 1.4 kg/h.
impactors 2+3+4 (Cont.)

SAMPLE 556 PSI/UA 47D ILL#6 ASH 1304C 1.4 KG/HR IMP 2+3+4
 NUMBER 556 DISK 52 FILE 129 - 132 PARTICLES
 RUN 1 DATE 26-APR-92 SUMMARY 132 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	10.3	5.	18.	29.	39.	9.	0.	0.
Fe - -	4.0	6.	28.	26.	37.	3.	0.	0.
Si AL -	4.1	8.	2.	25.	48.	17.	0.	0.
Si AL K	15.2	9.	13.	23.	35.	19.	1.	0.
Si S AL	5.9	0.	0.	9.	35.	36.	20.	0.
Si AL S	6.0	1.	20.	13.	34.	25.	6.	0.
Si AL Fe	11.0	15.	37.	27.	16.	3.	1.	0.
Si AL Ca	4.9	6.	47.	29.	12.	6.	0.	0.
OTHERS -	38.6	6.	21.	20.	25.	22.	6.	0.
TOTALS -	100.0	7.	21.	22.	29.	17.	4.	0.

TABLE 4-40. - Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11,
impactor #1 + cup

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 558 PSI/ARIZONA ASH ILLINOIS#6 2.4 KG/HR. 1368C PORT 11 IMP. #1 + CUP.

NUMBER 558 DISK 40 FILE 125 - 128 PARTICLES

RUN 1 DATE 26-DEC-91 SUMMARY 128 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.18274E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
149	Si - -	0.	0.	2.	95.	0.	0.	0.	2.	0.	0.	1.	0.	0.	0.	0.	14.1
46	Fe - -	1.	0.	0.	3.	0.	0.	0.	0.	1.	0.	96.	0.	0.	0.	0.	4.8
13	Ca - -	0.	0.	1.	1.	0.	1.	0.	0.	95.	0.	1.	0.	1.	0.	0.	0.7
55	Si Al -	1.	0.	31.	58.	0.	1.	0.	5.	1.	1.	3.	0.	0.	0.	0.	4.5
12	Al Si -	0.	0.	51.	45.	0.	0.	0.	3.	0.	0.	0.	0.	0.	0.	0.	0.8
41	Ca S -	0.	0.	0.	1.	0.	39.	0.	0.	57.	0.	2.	0.	0.	0.	0.	3.5
3	Si Fe -	0.	0.	3.	55.	0.	0.	0.	4.	3.	0.	36.	0.	0.	0.	0.	0.6
254	Si Al K	1.	0.	26.	59.	0.	1.	0.	8.	1.	0.	4.	0.	0.	0.	0.	20.9
52	Si Fe Al	0.	0.	16.	48.	0.	2.	0.	5.	2.	1.	25.	0.	0.	0.	0.	4.5
228	Si Al Fe	1.	0.	25.	50.	0.	3.	0.	6.	3.	1.	11.	0.	0.	0.	0.	20.1
28	Fe Si Al	0.	0.	12.	27.	0.	1.	0.	3.	2.	1.	54.	0.	0.	0.	0.	2.6
7	S Si Ca	0.	0.	12.	23.	0.	31.	4.	7.	13.	0.	8.	0.	3.	0.	0.	0.6
16	Ca S Si	0.	0.	4.	14.	0.	31.	0.	0.	48.	1.	2.	0.	0.	0.	0.	0.8
5	S Ca Si	0.	0.	4.	10.	2.	47.	1.	0.	28.	3.	3.	1.	0.	0.	0.	0.5
8	Si Ca S	0.	0.	9.	44.	0.	16.	0.	1.	24.	0.	6.	0.	0.	0.	0.	0.8
13	S Si Al	0.	0.	18.	25.	0.	40.	1.	1.	4.	3.	3.	0.	4.	0.	0.	0.6
21	Si Al S	0.	0.	23.	48.	1.	13.	0.	3.	6.	0.	5.	1.	0.	0.	0.	1.7
14	Si S Al	0.	0.	16.	41.	0.	28.	1.	2.	6.	0.	5.	0.	0.	0.	0.	1.0
4	Fe Ca Si	0.	0.	4.	8.	0.	0.	0.	0.	16.	0.	71.	0.	0.	0.	0.	0.5
37	Si Al Ca	1.	0.	29.	47.	0.	2.	0.	4.	10.	1.	5.	0.	0.	0.	0.	3.5
12	Si Ca Al	0.	1.	16.	43.	0.	4.	0.	2.	25.	1.	8.	0.	0.	0.	0.	0.9
8	Ca Si Al	0.	1.	14.	26.	0.	2.	0.	1.	51.	0.	4.	0.	0.	0.	0.	0.6
16	Ca S Fe	0.	0.	2.	4.	1.	21.	0.	0.	63.	0.	8.	0.	0.	0.	0.	1.1
9	Si Al Ti	0.	0.	22.	45.	0.	1.	0.	3.	5.	15.	7.	0.	0.	0.	0.	1.3
1	Si Cl Al	0.	0.	12.	37.	0.	5.	26.	10.	4.	0.	6.	0.	0.	0.	0.	0.7
121	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.0
1177	TOTALS -	1.	0.	17.	49.	0.	6.	1.	4.	8.	1.	13.	0.	0.	0.	0.	100.0

TABLE 4-40. - Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11,
impactor #1 + cup (Cont.)

SAMPLE # 558 PSI/ARIZONA ASH ILLINOIS#6 2.4 KG/HR. 1368C PORT 11 IMP. #1 + CUP.
NUMBER 558 DISK 40 FILE 125 - 128 PARTICLES
RUN 1 DATE 26-DEC-91 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	VOLUME %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	14.1	7.	27.	23.	35.	7.	2.	0.
Fe - -	4.8	18.	39.	18.	23.	2.	0.	0.
Si Al -	4.5	8.	34.	24.	21.	13.	0.	0.
Si Al K	20.9	5.	13.	25.	42.	12.	3.	0.
Si Fe Al	4.5	12.	26.	21.	31.	7.	3.	0.
Si Al Fe	20.1	37.	35.	15.	12.	1.	0.	0.
OTHERS -	31.1	17.	32.	24.	19.	7.	1.	0.
TOTALS -	100.0	16.	28.	22.	25.	7.	1.	0.

TABLE 4-41. - Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11, impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 559 PSI/ARIZONA ASH ILLINOIS#6 2.4 KG/HR 1368C PORT 11 IMPS 2+3+4.
 NUMBER 559 DISK 42 FILE 101 - 104 PARTICLES
 RUN 1 DATE 31-DEC-91 SUMMARY 104 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.19621E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
68	Si - -	0.	0.	2.	91.	0.	1.	0.	2.	1.	0.	3.	0.	0.	0.	0.	8.9
16	S - -	0.	0.	4.	3.	0.	81.	1.	0.	7.	0.	3.	0.	1.	0.	0.	2.0
41	Fe - -	0.	0.	2.	5.	0.	1.	0.	0.	2.	1.	89.	0.	0.	0.	0.	3.6
26	Si Al -	1.	0.	37.	55.	0.	1.	0.	3.	0.	0.	2.	0.	0.	0.	0.	2.0
57	Ca S -	0.	0.	0.	1.	0.	43.	0.	0.	54.	0.	1.	0.	0.	0.	0.	1.5
3	Si Fe -	0.	0.	0.	82.	0.	0.	0.	5.	0.	0.	13.	0.	0.	0.	0.	0.9
9	Fe Si -	0.	0.	3.	14.	0.	0.	0.	0.	0.	0.	82.	0.	0.	0.	0.	1.0
107	Ca S Si	0.	0.	6.	15.	0.	27.	0.	0.	45.	0.	6.	0.	0.	0.	0.	2.6
13	Ca Si S	0.	0.	13.	22.	0.	17.	1.	4.	38.	0.	6.	0.	0.	0.	0.	1.1
35	Ca S Fe	0.	0.	2.	4.	4.	22.	0.	0.	57.	0.	11.	0.	0.	0.	0.	3.7
14	Ca Fe S	0.	0.	2.	6.	6.	12.	0.	0.	53.	0.	19.	0.	0.	0.	0.	1.4
305	Si Al Fe	1.	0.	26.	48.	0.	4.	0.	5.	3.	1.	12.	0.	0.	0.	0.	34.1
47	Si Fe Al	1.	0.	19.	43.	0.	4.	0.	4.	4.	1.	24.	0.	0.	0.	0.	5.2
31	Fe Si Al	0.	0.	14.	24.	0.	3.	0.	2.	4.	3.	49.	0.	0.	0.	0.	3.3
10	Ca Fe Si	0.	0.	6.	14.	3.	6.	0.	1.	47.	1.	21.	0.	0.	0.	0.	1.2
6	Fe Ca Si	0.	0.	7.	14.	0.	7.	0.	1.	27.	0.	43.	0.	0.	0.	0.	0.8
12	Ca Si Fe	0.	0.	5.	23.	3.	6.	1.	1.	48.	1.	12.	0.	0.	0.	0.	1.1
60	Si Al K	1.	0.	27.	59.	0.	1.	0.	8.	0.	1.	3.	0.	0.	0.	0.	5.8
37	Si Al Ca	0.	0.	26.	43.	0.	4.	0.	3.	13.	1.	8.	0.	0.	0.	0.	3.9
8	Ca Si Al	2.	0.	14.	22.	0.	3.	0.	0.	49.	1.	8.	0.	0.	0.	0.	1.2
18	Si Ca Al	3.	0.	18.	38.	0.	6.	1.	2.	23.	1.	8.	0.	0.	0.	0.	1.8
17	Si S Al	0.	0.	23.	37.	0.	31.	2.	0.	3.	1.	4.	0.	0.	0.	0.	1.0
13	S Si Al	0.	0.	17.	20.	0.	49.	0.	0.	9.	2.	3.	0.	0.	0.	0.	1.3
27	Si Al S	0.	0.	30.	41.	0.	17.	0.	2.	5.	0.	3.	1.	2.	0.	0.	1.5
7	S Si Fe	1.	0.	2.	21.	6.	45.	0.	0.	11.	0.	13.	0.	0.	0.	0.	0.5
6	Si Al Na	10.	0.	21.	53.	0.	3.	0.	6.	2.	0.	5.	0.	0.	0.	0.	0.5
2	Fe Al Ca	0.	0.	22.	6.	0.	0.	0.	0.	16.	8.	47.	0.	0.	0.	0.	0.5
13	OTHERS -	0.	0.	12.	11.	1.	27.	0.	1.	22.	7.	18.	1.	1.	0.	0.	1.6
167	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.4

TABLE 4-41. - Arizona ash Illinois #6, 2.4 kg/h, 1368°C, port 11, impactors 2+3+4 (Cont.)

1178 TOTALS - 1. 0. 17. 41. 1. 9. 0. 3. 12. 1. 16. 0. 0. 0. 0. 100.0

SAMPLE # 559 PSI/ARIZONA ASH ILLINOIS#6 2.4 KG/HR 1368C PORT 11 IMPS 2+3+4.

NUMBER 559 DISK 42 FILE 101 - 104 PARTICLES

RUN 1 DATE 31-DEC-91 SUMMARY 104 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	8.9	61.	36.	2.	1.	0.	0.	0.
Si Al Fe	34.1	75.	23.	2.	0.	0.	0.	0.
Si Fe Al	5.2	69.	26.	4.	1.	0.	0.	0.
Si Al K	5.8	40.	54.	7.	0.	0.	0.	0.
OTHERS -	46.0	65.	19.	11.	5.	0.	0.	0.
TOTALS -	100.0	67.	24.	7.	2.	0.	0.	0.

**TABLE 4-42. - Arizona Illinois #6 ash on filter, 2.4 kg/h, 1368°C,
port 11, impactors 5+6+7**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 560 PSI/ARIZONA ILL#6 ASH ON FILTER 2.4KG/HR, 1368C, PORT 11, IMPS 5+6+7+
NUMBER 560 DISK 47 FILE 124 - 127 PARTICLES
RUN 1 DATE 18-MAR-92 SUMMARY 127 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.14710E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
10	S - -	0.	0.	1.	2.	0.	89.	2.	1.	1.	0.	1.	2.	1.	0.	0.	0.6
11	Fe - -	0.	0.	1.	2.	0.	1.	0.	0.	1.	0.	94.	1.	0.	0.	0.	0.6
25	Si - -	1.	0.	1.	89.	0.	3.	0.	2.	1.	1.	2.	0.	0.	0.	0.	2.1
9	Ca S -	0.	0.	0.	0.	0.	45.	0.	0.	54.	0.	0.	0.	0.	0.	0.	0.9
25	S Al -	0.	0.	25.	1.	0.	72.	0.	0.	0.	0.	2.	0.	0.	0.	0.	1.1
9	Si Mg -	0.	34.	0.	63.	0.	0.	0.	0.	2.	0.	1.	0.	0.	0.	0.	1.9
47	Si Fe S	1.	0.	12.	36.	0.	16.	0.	3.	11.	2.	19.	0.	0.	0.	0.	1.8
54	S Si Fe	2.	0.	8.	25.	0.	36.	0.	2.	10.	0.	15.	0.	0.	0.	0.	2.7
50	Si S Fe	1.	0.	10.	34.	0.	24.	0.	3.	11.	1.	15.	1.	0.	0.	0.	2.9
8	Fe Si S	0.	0.	8.	21.	0.	11.	0.	1.	8.	2.	49.	0.	0.	0.	0.	1.8
38	Si Al S	2.	0.	25.	39.	0.	17.	0.	3.	5.	0.	9.	0.	0.	0.	0.	6.2
28	Si S Al	2.	0.	16.	36.	0.	21.	0.	4.	9.	1.	12.	0.	0.	0.	0.	4.4
18	S Si Al	5.	0.	14.	24.	0.	43.	0.	2.	4.	2.	5.	0.	1.	0.	0.	0.7
80	S ⁺ Si Ca	4.	0.	4.	25.	1.	39.	0.	1.	16.	1.	9.	0.	0.	0.	0.	7.8
8	Ca Si S	0.	0.	8.	23.	2.	17.	1.	0.	40.	0.	11.	0.	0.	0.	0.	0.5
37	Si S Ca	0.	0.	9.	32.	0.	25.	0.	1.	18.	1.	13.	0.	0.	0.	0.	5.4
32	S Ca Si	1.	0.	6.	17.	1.	39.	0.	3.	25.	0.	8.	0.	0.	0.	0.	3.4
11	Ca S Si	0.	0.	10.	17.	3.	25.	0.	1.	36.	0.	8.	0.	0.	0.	0.	1.1
16	Si Ca S	1.	0.	9.	33.	0.	18.	0.	2.	23.	5.	10.	0.	0.	0.	0.	0.7
4	S Ca Fe	4.	0.	2.	11.	0.	42.	0.	0.	24.	2.	15.	0.	0.	0.	0.	0.5
5	Fe Ca S	0.	0.	9.	8.	4.	15.	3.	4.	23.	4.	30.	0.	2.	0.	0.	0.6
11	Ca S Fe	0.	0.	1.	6.	3.	28.	0.	2.	46.	0.	14.	0.	0.	0.	0.	1.2
9	Si Ca Al	0.	0.	18.	36.	0.	10.	0.	2.	20.	1.	11.	1.	0.	0.	0.	1.1
13	Si Al Ca	5.	0.	24.	36.	0.	7.	0.	2.	16.	1.	8.	0.	0.	0.	0.	0.8
41	Si Fe Ca	0.	0.	14.	32.	0.	12.	0.	3.	17.	2.	21.	0.	0.	0.	0.	4.4
29	Si Ca Fe	1.	0.	13.	35.	0.	11.	0.	2.	22.	1.	17.	0.	0.	0.	0.	1.6
10	Ca Si Fe	0.	0.	8.	17.	2.	9.	0.	2.	48.	0.	13.	0.	0.	0.	0.	1.2
88	Si Fe Al	0.	0.	17.	37.	0.	10.	0.	3.	9.	1.	22.	0.	0.	0.	0.	5.1
138	Si Al Fe	1.	0.	24.	43.	0.	8.	0.	3.	6.	1.	15.	0.	0.	0.	0.	12.9
6	Fe Si Al	0.	0.	16.	31.	0.	7.	0.	2.	10.	1.	34.	0.	0.	0.	0.	1.9
27	S Fe K	2.	0.	0.	1.	1.	57.	0.	12.	1.	0.	26.	0.	0.	0.	0.	1.8
8	Si S Na	15.	0.	9.	29.	0.	23.	0.	3.	8.	0.	12.	0.	0.	0.	0.	2.4
16	S Si Na	18.	0.	5.	25.	0.	34.	0.	1.	11.	0.	6.	0.	0.	0.	0.	1.1

TABLE 4-42. - Arizona Illinois #6 ash on filter. 2.4 kg/h. 1368°C.
port 11. impactors 5+6+7 (Cont.)

17	S	Na	Al	25.	0.	16.	2.	0.	50.	0.	1.	3.	1.	2.	0.	0.	0.	0.	0.8
4	S	Al	Ca	0.	8.	21.	2.	0.	40.	0.	0.	16.	2.	11.	0.	0.	0.	0.	0.6
63	OTHERS	-		5.	0.	10.	17.	2.	25.	1.	3.	20.	4.	12.	1.	0.	0.	0.	8.0
152	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																		7.1
1157	TOTALS	-		3.	1.	12.	29.	1.	22.	1.	3.	13.	1.	14.	0.	0.	0.	0.	100.0

SAMPLE 560 PSI/ARIZONA ILL#6 ASH ON FILTER 2.4KG/HR, 1368C, PORT 11, IMPS 5+6+7+
NUMBER 560 DISK 47 FILE 124 - 127 PARTICLES
RUN 1 DATE 18-MAR-92 SUMMARY 127 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si Al S	6.2	46.	47.	6.	0.	1.	0.	0.
Si S Al	4.4	30.	63.	7.	0.	1.	0.	0.
S Si Ca	7.8	10.	57.	16.	13.	3.	0.	0.
Si S Ca	5.4	5.	78.	12.	4.	2.	0.	0.
Si Fe Ca	4.4	9.	58.	16.	16.	1.	0.	0.
Si Fe Al	5.1	31.	24.	30.	15.	1.	0.	0.
Si Al Fe	12.9	61.	26.	9.	4.	0.	0.	0.
OTHERS -	8.0	64.	32.	1.	3.	0.	0.	0.
OTHERS -	45.9	34.	28.	22.	11.	5.	1.	0.
TOTALS -	100.0	36.	37.	16.	9.	3.	0.	0.

**TABLE 4-43. - Arizona Illinois #6 run 47h, 2.4 kg/h, 1368°C,
port 5, impactors 1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 561 PSI/UA ILL #6 RUN 47H 2.4 KG/HR 1368C PORT 5, IMP 1+CUP.
NUMBER 561 DISK 52 FILE 133 - 136 PARTICLES
RUN 1 DATE 28-APR-92 SUMMARY 136 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.24891E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
33	Na - -	94.	0.	0.	2.	0.	2.	1.	0.	0.	0.	0.	0.	0.	0.	0.	2.5
149	Si - -	0.	0.	1.	95.	0.	0.	0.	2.	1.	0.	1.	0.	0.	0.	0.	14.9
41	Fe - -	0.	0.	0.	3.	0.	0.	0.	0.	0.	0.	96.	0.	0.	0.	0.	4.8
16	Ca - -	0.	0.	1.	2.	0.	2.	0.	0.	93.	0.	1.	0.	0.	0.	0.	1.4
4	Fe Si -	0.	0.	1.	16.	0.	0.	0.	1.	0.	0.	82.	0.	0.	0.	0.	0.5
48	Si Al -	0.	0.	29.	62.	0.	1.	0.	4.	1.	1.	2.	0.	0.	0.	0.	5.5
6	Al Si -	0.	0.	49.	41.	0.	1.	0.	3.	2.	0.	4.	0.	0.	0.	0.	0.5
16	Ca S -	0.	0.	0.	1.	0.	38.	0.	1.	60.	0.	0.	0.	0.	0.	0.	0.6
39	Si Fe Al	0.	0.	17.	45.	0.	2.	0.	4.	4.	1.	26.	0.	0.	0.	0.	2.7
257	Si Al Fe	1.	0.	27.	50.	0.	1.	0.	5.	3.	1.	11.	0.	0.	0.	0.	20.8
26	Fe Si Al	0.	0.	12.	29.	0.	2.	0.	1.	2.	1.	53.	0.	0.	0.	0.	2.5
25	Si Al S	0.	0.	23.	51.	0.	12.	0.	2.	6.	1.	3.	0.	0.	0.	0.	1.9
15	Si S Al	0.	0.	16.	48.	0.	22.	0.	5.	4.	0.	3.	0.	0.	0.	0.	0.8
6	Si Al Ti	0.	0.	26.	38.	0.	0.	0.	3.	9.	15.	8.	0.	0.	0.	0.	0.8
167	Si Al K	1.	0.	27.	57.	0.	1.	0.	8.	1.	1.	4.	0.	0.	0.	0.	15.6
16	S Ca Si	0.	0.	8.	17.	0.	41.	0.	3.	26.	2.	3.	1.	0.	0.	0.	0.5
9	Si Ca S	0.	0.	11.	44.	0.	16.	0.	3.	20.	0.	6.	0.	0.	0.	0.	0.8
8	Si S Ca	0.	0.	7.	49.	0.	22.	0.	0.	12.	0.	4.	0.	4.	0.	0.	1.0
14	Ca S Si	1.	0.	6.	18.	0.	30.	0.	1.	40.	0.	3.	0.	1.	0.	0.	1.1
5	Ca Si S	0.	0.	10.	19.	0.	14.	0.	1.	51.	0.	6.	0.	0.	0.	0.	0.6
5	Fe Si Ca	0.	0.	8.	24.	0.	7.	0.	5.	13.	5.	38.	0.	0.	0.	0.	0.6
11	Si Ca Al	0.	0.	15.	44.	0.	7.	0.	1.	25.	2.	6.	0.	0.	0.	0.	2.4
56	Si Al Ca	1.	0.	26.	44.	0.	3.	0.	4.	13.	1.	6.	0.	0.	0.	0.	6.4
7	Ca Si Al	0.	0.	12.	19.	0.	2.	0.	0.	58.	2.	7.	0.	0.	0.	0.	0.6
1	Si Cl Al	13.	0.	20.	23.	0.	5.	20.	7.	6.	0.	4.	2.	0.	0.	0.	0.8
8	Si Al Na	9.	0.	27.	51.	0.	1.	0.	6.	0.	0.	6.	0.	0.	0.	0.	0.9
2	Na Si Al	45.	0.	18.	24.	0.	2.	0.	4.	2.	0.	5.	0.	1.	0.	0.	0.5
21	OTHERS -	0.	0.	5.	18.	0.	10.	0.	2.	25.	9.	30.	0.	0.	0.	0.	1.2
131	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.4
1142	TOTALS -	4.	0.	17.	49.	0.	4.	0.	4.	8.	1.	13.	0.	0.	0.	0.	100.0

**TABLE 4-43. - Arizona Illinois #6 run 47h. 2.4 kg/h. 1368°C.
port 5. impactors 1 + cup (Cont.)**

SAMPLE 561 PSI/UA ILL #6 RUN 47H 2.4 KG/HR 1368C PORT 5, IMP 1+CUP.
NUMBER 561 DISK 52 FILE 133 - 136 PARTICLES
RUN 1 DATE 28-APR-92 SUMMARY 136 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	14.9	3.	24.	44.	23.	5.	1.	0.
Fe - -	4.8	7.	22.	25.	42.	2.	1.	0.
Si Al -	5.5	2.	19.	23.	50.	7.	0.	0.
Si Al K	15.6	1.	27.	30.	30.	10.	2.	0.
Si Al Fe	20.8	20.	38.	26.	13.	4.	0.	0.
Si Al Ca	6.4	3.	41.	32.	23.	1.	0.	0.
OTHERS -	32.0	9.	14.	25.	34.	15.	3.	0.
TOTALS -	100.0	8.	25.	29.	28.	8.	2.	0.

**TABLE 4-44. - Arizona Illinois #6 run 47h. 2.4 kg/h. 1368°C.
port 5. impactors 2+3+4**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 562 PSI/UA ILL#6 RUN 47H 2.4 KG/HR 1368C PORT 5 IMP 2+3+4
NUMBER 562 DISK 58 FILE 101 - 104 PARTICLES
RUN 1 DATE 13-MAY-92 SUMMARY 104 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.39955E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
14	Na - -	95.	0.	0.	1.	0.	1.	1.	0.	1.	0.	0.	0.	0.	0.	0.	1.2
126	Si - -	0.	0.	2.	93.	0.	1.	0.	1.	1.	0.	1.	0.	0.	0.	0.	10.7
32	Fe - -	0.	0.	2.	5.	0.	0.	0.	0.	1.	1.	91.	0.	0.	0.	0.	3.5
41	Si Al -	0.	0.	29.	63.	0.	1.	0.	4.	1.	0.	2.	0.	0.	0.	0.	1.4
36	Ca S -	0.	0.	0.	2.	0.	44.	0.	0.	52.	0.	1.	0.	0.	0.	0.	0.7
8	Fe Si -	0.	0.	3.	20.	0.	2.	0.	2.	3.	0.	70.	0.	0.	0.	0.	0.9
3	Si S Fe	0.	0.	9.	52.	0.	14.	0.	6.	7.	1.	11.	0.	0.	0.	0.	0.5
6	S Si Fe	0.	0.	0.	16.	0.	71.	0.	0.	2.	0.	10.	0.	0.	0.	0.	0.5
2	Cl S K	0.	0.	0.	5.	0.	26.	50.	15.	5.	0.	0.	0.	0.	0.	0.	0.6
11	Si S Al	0.	0.	15.	46.	0.	28.	0.	3.	0.	1.	7.	0.	0.	0.	0.	1.2
19	Si Fe Al	1.	0.	18.	43.	0.	4.	0.	2.	2.	3.	29.	0.	0.	0.	0.	2.9
277	Si Al Fe	1.	0.	28.	49.	0.	1.	0.	5.	3.	1.	12.	0.	0.	0.	0.	40.2
26	Fe Si Al	0.	0.	16.	27.	0.	0.	0.	0.	3.	2.	52.	0.	0.	0.	0.	1.8
20	Ca Si S	0.	0.	11.	27.	0.	17.	0.	1.	34.	0.	9.	0.	0.	0.	0.	0.6
114	Ca S Si	0.	0.	7.	15.	0.	32.	0.	0.	40.	0.	5.	0.	0.	0.	0.	2.4
26	Si Ca S	0.	0.	9.	39.	0.	19.	0.	2.	24.	0.	7.	0.	0.	0.	0.	0.6
59	Si Al Ca	0.	0.	23.	50.	0.	1.	0.	3.	14.	1.	8.	0.	0.	0.	0.	4.6
17	Ca Si Al	0.	0.	16.	28.	1.	1.	0.	0.	47.	0.	7.	0.	0.	0.	0.	1.6
12	Si Ca Al	0.	0.	18.	41.	0.	6.	1.	2.	21.	1.	10.	0.	0.	0.	0.	0.7
3	Al Ca Si	0.	0.	33.	22.	0.	3.	0.	0.	26.	1.	15.	0.	0.	0.	0.	0.6
129	Si Al K	1.	0.	27.	60.	0.	0.	0.	8.	0.	0.	4.	0.	0.	0.	0.	7.2
12	Si Al Na	9.	0.	27.	47.	0.	1.	0.	6.	2.	1.	7.	0.	0.	0.	0.	1.7
7	Si Al Ti	0.	0.	26.	54.	0.	0.	0.	8.	1.	10.	0.	0.	0.	0.	0.	1.5
4	Fe Ca Si	0.	0.	10.	16.	0.	0.	0.	0.	23.	0.	51.	0.	0.	0.	0.	0.6
11	Ca Si Fe	0.	0.	11.	23.	2.	8.	0.	1.	41.	0.	13.	0.	0.	0.	0.	2.9
4	Si Fe Ca	0.	0.	8.	58.	0.	2.	0.	0.	16.	0.	16.	0.	0.	0.	0.	1.4
4	Si Fe K	0.	0.	3.	61.	0.	0.	0.	10.	2.	4.	20.	0.	0.	0.	0.	0.6
134	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.6
1157	TOTALS -	2.	0.	19.	47.	0.	4.	1.	4.	8.	1.	14.	0.	0.	0.	0.	100.0

**TABLE 4-44. - Arizona Illinois #6 run 47h. 2.4 kg/h. 1368°C.
port 5. impactors 2+3+4 (Cont.)**

SAMPLE 562 PSI/UA ILL#6 RUN 47H 2.4 KG/HR 1368C PORT 5 IMP 2+3+4
 NUMBER 562 DISK 58 FILE 101 - 104 PARTICLES
 RUN 1 DATE 13-MAY-92 SUMMARY 104 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	10.7	34.	42.	12.	13.	0.	0.	0.
Si Al Fe	40.2	61.	35.	3.	1.	0.	0.	0.
Si Al Ca	4.6	48.	31.	15.	7.	0.	0.	0.
Si Al K	7.2	19.	45.	23.	14.	0.	0.	0.
OTHERS -	37.3	39.	28.	17.	11.	4.	0.	0.
TOTALS -	100.0	46.	34.	11.	7.	2.	0.	0.

**TABLE 4-45. - PSIT/Arizona ash Illinois #6 soap. 1.8 kg/h. port 11.
impactor #1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 582 PSI/ARIZONA ASH ILL#6 SOAP 1.8KG/HR 1310C PORT 11 IMP. #1 + CUP.
NUMBER 582 DISK 42 FILE 109 - 112 PARTICLES
RUN 1 DATE 5-JAN-92 SUMMARY 112 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.75981E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
32	S - -	0.	0.	2.	3.	0.	85.	1.	1.	2.	1.	5.	0.	0.	0.	0.	2.5
2	Ti - -	0.	0.	0.	2.	0.	4.	0.	0.	0.	94.	0.	0.	0.	0.	0.	0.5
41	Si - -	1.	0.	1.	93.	0.	0.	0.	1.	0.	0.	4.	0.	0.	0.	0.	4.3
15	Fe - -	0.	0.	3.	5.	0.	0.	0.	0.	1.	2.	89.	0.	0.	0.	0.	0.9
9	S Fe -	0.	0.	1.	1.	0.	82.	0.	0.	0.	0.	16.	0.	0.	0.	0.	0.6
12	S Si -	0.	0.	1.	18.	0.	79.	0.	1.	1.	0.	1.	0.	0.	0.	0.	0.7
34	Ca S -	0.	0.	0.	1.	0.	44.	0.	0.	53.	0.	1.	0.	0.	0.	0.	4.0
7	S Ca -	0.	0.	0.	2.	0.	57.	0.	0.	41.	0.	0.	0.	0.	0.	0.	0.7
19	Si Al -	0.	0.	39.	57.	0.	0.	0.	2.	0.	1.	1.	0.	0.	0.	0.	1.3
46	S Fe Si	0.	0.	4.	14.	0.	57.	1.	1.	1.	1.	18.	0.	1.	0.	0.	4.7
75	S Si Fe	0.	0.	6.	19.	0.	58.	0.	2.	1.	1.	12.	0.	0.	0.	0.	6.0
66	S Si Al	0.	0.	13.	23.	0.	54.	1.	2.	1.	1.	5.	0.	0.	0.	0.	5.8
27	Si S Al	0.	0.	16.	44.	0.	26.	0.	3.	2.	1.	7.	1.	0.	0.	0.	2.3
10	Si Al S	0.	0.	27.	48.	0.	14.	0.	6.	1.	1.	3.	0.	0.	0.	0.	1.7
11	S Al Si	0.	0.	15.	13.	1.	62.	1.	1.	1.	0.	5.	0.	0.	0.	0.	1.0
4	Ca S Si	0.	0.	4.	12.	0.	34.	0.	0.	43.	0.	7.	0.	0.	0.	0.	0.8
9	S Si Ca	3.	0.	6.	18.	0.	53.	0.	2.	12.	0.	5.	0.	1.	0.	0.	0.8
134	Si Al Fe	2.	0.	25.	50.	0.	0.	0.	6.	1.	1.	14.	0.	0.	0.	0.	11.4
144	Fe Si Al	0.	0.	15.	26.	0.	0.	0.	2.	5.	5.	46.	0.	0.	0.	0.	11.3
160	Si Fe Al	1.	0.	18.	42.	0.	1.	0.	4.	3.	4.	27.	0.	0.	0.	0.	11.2
39	Si Al K	0.	0.	28.	58.	0.	1.	0.	8.	0.	0.	4.	0.	0.	0.	0.	2.7
6	S Fe Ca	0.	0.	1.	12.	0.	37.	0.	10.	17.	0.	22.	0.	0.	0.	0.	1.3
8	S Si K	0.	0.	3.	19.	0.	63.	0.	10.	1.	0.	3.	0.	0.	0.	0.	0.6
18	S Fe Al	0.	0.	13.	4.	0.	56.	0.	8.	0.	1.	19.	0.	0.	0.	0.	2.6
6	S Al Fe	0.	0.	12.	8.	0.	62.	1.	1.	2.	3.	10.	0.	1.	0.	0.	0.5
6	Si Fe Ca	0.	0.	12.	38.	0.	1.	0.	1.	17.	4.	26.	0.	0.	0.	0.	0.5
9	Fe Si Ca	0.	0.	11.	26.	0.	1.	0.	0.	17.	3.	42.	0.	0.	0.	0.	1.1
9	S Fe K	0.	0.	8.	7.	0.	59.	0.	10.	0.	1.	14.	1.	0.	0.	0.	1.0
6	Si Fe Ti	2.	0.	9.	45.	0.	0.	0.	4.	3.	12.	26.	0.	0.	0.	0.	1.2

**TABLE 4-45. - PSIT/Arizona ash Illinois #6 soap, 1.8 kg/h. port 11.
impactors #1 + cup (Cont.)**

6	S	Si	Ti	0.	0.	2.	14.	0.	66.	0.	1.	2.	11.	4.	0.	0.	0.	0.	0.5
2	Al	Cu	S	0.	0.	36.	0.	0.	16.	4.	0.	7.	2.	1.	34.	0.	0.	0.	0.7
3	Si	Fe	K	0.	0.	7.	66.	0.	0.	0.	10.	2.	2.	14.	0.	0.	0.	0.	0.7
56	OTHERS	-		3.	2.	13.	27.	0.	12.	2.	4.	6.	5.	23.	1.	1.	0.	0.	5.5
111	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																		9.2
1122	TOTALS	-		1.	0.	13.	30.	0.	25.	1.	3.	6.	3.	18.	1.	0.	0.	0.	100.0

SAMPLE # 582 PSI/ARIZONA ASH ILL#6 SOAP 1.8KG/HR 1310C PORT 11 IMP. #1 + CUP.

NUMBER 582 DISK 42 FILE 109 - 112 PARTICLES

RUN 1 DATE 5-JAN-92 SUMMARY 112 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	4.3	8.	52.	22.	13.	4.	0.	0.
S Fe Si	4.7	2.	19.	19.	44.	16.	0.	0.
S Si Fe	6.0	2.	10.	32.	26.	30.	0.	0.
S Si Al	5.8	3.	0.	27.	62.	8.	0.	0.
Si Al Fe	11.4	29.	39.	21.	10.	1.	0.	0.
Fe Si Al	11.3	69.	21.	6.	4.	0.	0.	0.
Si Fe Al	11.2	42.	28.	19.	9.	0.	2.	0.
OTHERS -	5.5	34.	44.	14.	8.	0.	0.	0.
OTHERS -	39.9	8.	26.	27.	33.	5.	1.	0.
TOTALS -	100.0	22.	26.	22.	24.	5.	1.	0.

TABLE 4-46. - PSIT/Arizona Illinois #6 soap ash, 1.8 kg/h. port 11, impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 583 PSI/ARIZONA ILL#6 SOAP ASH 1.8KG/HR 1310C PORT 11 IMP. 2+3+4.
 NUMBER 583 DISK 43 FILE 127 - 130 PARTICLES
 RUN 1 DATE 22-JAN-92 SUMMARY 130 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>5000 0

TOTAL Volume FACTOR: 0.16238E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
12	S - -	1.	0.	4.	5.	0.	81.	0.	0.	3.	0.	3.	0.	1.	0.	0.	1.7
2	Cl - -	0.	0.	5.	0.	0.	3.	91.	0.	0.	0.	0.	1.	0.	0.	0.	2.1
21	Si - -	0.	0.	0.	91.	0.	0.	0.	2.	0.	0.	5.	0.	0.	0.	0.	2.8
62	Fe - -	0.	0.	3.	5.	0.	2.	0.	0.	1.	1.	87.	0.	0.	0.	0.	3.0
27	Ca S -	0.	0.	1.	0.	0.	46.	0.	0.	50.	0.	2.	0.	0.	0.	0.	2.5
1	Ca S Ti	0.	0.	0.	0.	0.	38.	0.	0.	39.	23.	0.	0.	0.	0.	0.	0.9
1	Ca S Al	0.	0.	16.	8.	0.	34.	7.	0.	35.	0.	0.	0.	0.	0.	0.	1.0
9	Fe S Al	0.	0.	15.	11.	1.	27.	0.	3.	2.	2.	37.	0.	0.	0.	0.	0.8
20	S Fe Al	0.	0.	16.	3.	1.	45.	0.	7.	2.	1.	24.	0.	0.	0.	0.	1.5
6	S Al Fe	0.	0.	23.	12.	0.	33.	0.	1.	1.	0.	19.	0.	11.	0.	0.	0.5
13	Si Al S	0.	0.	22.	42.	0.	17.	0.	3.	3.	5.	4.	2.	1.	0.	0.	0.5
16	S Si Al	0.	0.	15.	20.	0.	56.	2.	4.	1.	0.	2.	0.	0.	0.	0.	1.7
10	Si S Al	0.	0.	22.	35.	0.	24.	0.	5.	1.	0.	12.	0.	0.	0.	0.	0.9
7	S Si Ca	0.	0.	3.	34.	1.	38.	0.	1.	15.	7.	1.	0.	0.	0.	0.	0.5
16	S Si Fe	0.	0.	10.	25.	0.	43.	0.	5.	1.	1.	15.	0.	0.	0.	0.	1.2
12	Fe Si S	0.	0.	12.	20.	1.	15.	1.	4.	3.	4.	40.	0.	0.	0.	0.	1.3
11	Fe S Si	1.	1.	5.	20.	0.	22.	0.	2.	2.	8.	39.	0.	0.	0.	0.	0.5
22	S Fe Si	0.	0.	3.	16.	0.	51.	2.	3.	2.	2.	22.	0.	0.	0.	0.	1.4
11	Si S Fe	0.	0.	9.	39.	0.	26.	1.	0.	0.	1.	22.	0.	0.	0.	0.	0.6
5	Si Fe S	0.	0.	14.	30.	0.	20.	0.	4.	5.	4.	24.	0.	0.	0.	0.	1.1
10	S Ca Fe	0.	0.	3.	5.	0.	51.	0.	1.	28.	0.	12.	0.	0.	0.	0.	1.6
9	Ca S Fe	0.	0.	0.	4.	0.	35.	0.	0.	51.	0.	10.	0.	0.	0.	0.	0.9
171	Si Fe Al	1.	0.	18.	42.	0.	1.	0.	4.	3.	3.	26.	0.	0.	0.	0.	15.6
113	Si Al Fe	2.	0.	25.	46.	0.	1.	0.	5.	2.	2.	17.	0.	1.	0.	0.	11.9
318	Fe Si Al	0.	0.	15.	25.	0.	1.	0.	2.	4.	5.	48.	0.	0.	0.	0.	29.1
16	Fe Al Si	0.	0.	20.	16.	0.	3.	0.	1.	5.	4.	51.	0.	0.	0.	0.	1.2
6	Fe Si Ca	0.	0.	9.	26.	0.	1.	1.	0.	18.	4.	41.	0.	0.	0.	0.	1.0
2	S Fe P	0.	0.	0.	10.	15.	40.	0.	11.	0.	0.	25.	0.	0.	0.	0.	0.6
2	Cl Ca S	0.	0.	0.	0.	0.	12.	49.	6.	27.	0.	0.	0.	0.	0.	0.	0.6
10	Fe Ti Si	1.	0.	10.	15.	0.	2.	0.	0.	4.	19.	49.	0.	1.	0.	0.	0.7
16	Fe Si Ti	0.	0.	11.	20.	0.	1.	0.	1.	4.	15.	48.	0.	0.	0.	0.	1.2

**TABLE 4-46. - PSIT/Arizona Illinois #6 soap ash, 1.8 kg/h. port 11,
impactors 2+3+4 (Cont.)**

22 OTHERS -	1.	5.	10.	24.	2.	16.	1.	1.	10.	6.	23.	0.	0.	0.	0.	2.0
125 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.4

1105 TOTALS -	1.	0.	14.	27.	0.	12.	3.	3.	6.	3.	29.	0.	0.	0.	0.	100.0

SAMPLE # 583 PSI/ARIZONA ILL#6 SOAP ASH 1.8KG/HR 1310C PORT 11 IMP. 2+3+4.
NUMBER 583 DISK 43 FILE 127 - 130 PARTICLES
RUN 1 DATE 22-JAN-92 SUMMARY 130 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.

Si Fe Al	15.6	84.	15.	2.	0.	0.	0.	0.
Si Al Fe	11.9	71.	27.	2.	0.	0.	0.	0.
Fe Si Al	29.1	85.	14.	1.	0.	0.	0.	0.

OTHERS -	43.4	44.	25.	14.	6.	3.	8.	0.

TOTALS -	100.0	65.	20.	7.	2.	2.	3.	0.

TABLE 4-47. - PSIT/Arizona Illinois #6 soap, 1.8 kg/h, 1310°C, port 11, impactors 5+6+7+8+AF

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 584 PSI/ARIZONA ILL#6 SOAP, 1.8KG/HR, 1310C, PORT 11, IMPS 5+6+7+8+AF

NUMBER 584 DISK 49 FILE 126 - 129 PARTICLES

RUN 1 DATE 31-MAR-92 SUMMARY 129 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.52788E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
3	S - -	0.	0.	0.	6.	0.	82.	0.	3.	1.	3.	1.	0.	5.	0.	0.	0.6
10	Fe - -	0.	0.	0.	1.	0.	0.	0.	0.	1.	1.	96.	0.	0.	0.	0.	0.6
136	Fe S Si	0.	0.	6.	17.	0.	26.	0.	9.	3.	2.	36.	0.	0.	0.	0.	12.3
35	S Si Fe	0.	0.	7.	23.	0.	39.	0.	5.	5.	1.	19.	0.	0.	0.	0.	4.1
215	S Fe Si	0.	0.	8.	17.	1.	36.	0.	9.	3.	2.	25.	0.	0.	0.	0.	20.0
133	Fe Si S	0.	0.	7.	25.	0.	16.	0.	6.	2.	3.	40.	0.	0.	0.	0.	12.3
53	Si Fe S	0.	0.	8.	34.	0.	18.	0.	8.	4.	2.	27.	0.	0.	0.	0.	4.3
6	Cl S K	0.	0.	0.	2.	0.	25.	51.	19.	3.	0.	0.	0.	0.	0.	0.	0.6
2	Si Al Cl	0.	0.	34.	41.	0.	0.	17.	8.	0.	0.	0.	0.	0.	0.	0.	0.6
136	S Fe K	0.	0.	3.	8.	0.	48.	0.	14.	1.	1.	25.	0.	0.	0.	0.	10.8
11	S K Fe	0.	0.	11.	8.	0.	44.	0.	21.	0.	0.	15.	0.	0.	0.	0.	0.8
9	Fe S K	0.	0.	5.	11.	0.	33.	0.	13.	0.	0.	36.	0.	0.	0.	0.	0.7
13	S K Al	1.	0.	15.	5.	0.	45.	0.	20.	2.	0.	11.	0.	0.	0.	0.	0.8
8	S K Si	0.	0.	6.	15.	0.	42.	0.	21.	2.	0.	11.	2.	0.	0.	0.	0.5
22	S Fe Al	0.	0.	16.	11.	0.	39.	0.	8.	4.	1.	21.	0.	0.	0.	0.	1.0
72	Fe Si Al	0.	0.	14.	27.	0.	5.	0.	4.	3.	3.	43.	0.	0.	0.	0.	6.9
62	Si Fe Al	0.	1.	17.	38.	0.	6.	0.	5.	3.	2.	28.	0.	0.	0.	0.	7.0
2	S Si Al	0.	0.	18.	21.	0.	24.	4.	12.	3.	4.	15.	0.	0.	0.	0.	1.0
6	Fe Si Ca	0.	0.	12.	24.	0.	12.	0.	1.	15.	1.	35.	0.	0.	0.	0.	0.8
9	Fe Si K	0.	0.	7.	29.	0.	4.	0.	11.	3.	0.	44.	0.	2.	0.	0.	0.5
5	S Fe Ti	0.	0.	11.	2.	0.	42.	0.	2.	0.	21.	22.	0.	0.	0.	0.	0.6
1	S Zn Fe	0.	0.	0.	13.	0.	42.	0.	11.	0.	0.	15.	0.	19.	0.	0.	1.0
5	S Ca Si	0.	0.	1.	15.	0.	36.	1.	5.	27.	0.	13.	0.	0.	0.	0.	1.3
1	S Na Fe	21.	0.	8.	8.	0.	28.	0.	11.	6.	4.	13.	0.	0.	0.	0.	0.6
4	Si Fe Ti	0.	0.	5.	47.	0.	9.	0.	7.	1.	11.	21.	0.	0.	0.	0.	0.5
143	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.7
1102	TOTALS -	1.	0.	8.	20.	0.	26.	2.	8.	4.	2.	28.	0.	0.	0.	0.	100.0

TABLE 4-47. - PSIT/Arizona Illinois #6 soap, 1.8 kg/h, 1310°C, port 11,
impactors 5+6+7+8+AF (Cont.)

SAMPLE 584 PSI/ARIZONA ILL#6 SOAP, 1.8KG/HR, 1310C, PORT 11, IMPS 5+6+7+8+AF
NUMBER 584 DISK 49 FILE 126 - 129 PARTICLES
RUN 1 DATE 31-MAR-92 SUMMARY 129 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Fe S Si	12.3	15.	34.	22.	26.	2.	0.	0.
S Si Fe	4.1	13.	62.	18.	5.	3.	0.	0.
S Fe Si	20.0	11.	35.	23.	29.	1.	0.	0.
Fe Si S	12.3	23.	49.	23.	5.	0.	0.	0.
Si Fe S	4.3	32.	43.	23.	2.	0.	0.	0.
S Fe K	10.8	16.	45.	32.	7.	0.	0.	0.
Fe Si Al	6.9	64.	30.	5.	0.	0.	0.	0.
Si Fe Al	7.0	63.	36.	2.	0.	0.	0.	0.
OTHERS -	22.3	27.	28.	19.	14.	10.	3.	0.
TOTALS -	100.0	25.	37.	20.	14.	3.	1.	0.

TABLE 4-48. - PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11, impactors #1 + cup

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 564 PSI/ARIZONA ASH BEULAH 1.6KG/HR. 1160C PORT 11 IMP.#1 + CUP
 NUMBER 564 DISK 42 FILE 105 - 108 PARTICLES
 RUN 1 DATE 4-JAN-92 SUMMARY 108 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.15909E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
46	Si - -	6.	0.	0.	90.	0.	2.	0.	0.	2.	0.	0.	0.	0.	0.	0.	4.9
18	Fe - -	0.	0.	0.	1.	0.	0.	0.	0.	3.	0.	95.	0.	0.	0.	0.	1.4
64	Ca - -	1.	3.	5.	5.	0.	4.	0.	0.	79.	1.	4.	0.	0.	0.	0.	6.4
4	Ca Fe -	0.	0.	2.	2.	0.	3.	0.	0.	68.	1.	24.	0.	0.	0.	0.	0.5
2	Si Ca -	2.	0.	0.	75.	0.	3.	0.	1.	18.	0.	0.	0.	0.	0.	0.	0.7
19	Ca S -	0.	1.	0.	1.	0.	23.	0.	0.	74.	0.	0.	0.	0.	0.	0.	1.1
5	Cu Zn -	0.	0.	0.	0.	0.	0.	1.	0.	0.	0.	0.	76.	23.	0.	0.	0.5
7	Ca Fe Si	0.	2.	7.	13.	0.	2.	0.	0.	51.	1.	24.	0.	0.	0.	0.	0.9
8	Ca Si Fe	2.	4.	10.	18.	0.	2.	0.	0.	50.	1.	13.	0.	0.	0.	0.	0.8
10	Si Al Fe	1.	0.	24.	50.	0.	2.	0.	4.	5.	0.	13.	0.	0.	0.	0.	0.7
302	Ca Si Al	4.	2.	16.	22.	0.	4.	0.	0.	46.	1.	3.	0.	0.	0.	0.	25.9
61	Si Al Ca	10.	0.	26.	39.	0.	3.	0.	1.	17.	1.	3.	0.	0.	0.	0.	5.4
43	Si Ca Al	11.	0.	20.	32.	0.	7.	0.	1.	25.	1.	3.	0.	0.	0.	0.	2.5
34	Ca Al Si	1.	2.	17.	14.	0.	3.	0.	0.	59.	1.	3.	0.	0.	0.	0.	2.9
124	Si Al Na	21.	0.	30.	37.	0.	1.	0.	0.	9.	0.	1.	0.	0.	0.	0.	8.6
22	Si Na Al	29.	0.	26.	37.	0.	2.	0.	0.	6.	0.	0.	0.	0.	0.	0.	1.4
8	Ca Si Mg	0.	9.	7.	14.	0.	2.	0.	0.	65.	1.	3.	0.	0.	0.	0.	0.7
17	Ca Mg Si	0.	19.	9.	12.	0.	4.	0.	0.	52.	0.	4.	0.	0.	0.	0.	1.4
11	Ca S Al	2.	4.	11.	6.	0.	23.	2.	1.	50.	0.	2.	0.	0.	0.	0.	1.0
7	Ca Si Na	15.	1.	13.	18.	0.	13.	0.	0.	38.	0.	2.	0.	0.	0.	0.	0.6
13	Si Ca Na	12.	0.	6.	54.	0.	4.	0.	0.	20.	1.	3.	0.	0.	0.	0.	1.5
6	Si Na Ca	21.	0.	6.	50.	0.	5.	0.	0.	15.	1.	2.	0.	0.	0.	0.	0.5
8	Si Al K	1.	0.	26.	55.	0.	1.	0.	8.	3.	1.	5.	0.	0.	0.	0.	0.8
89	Ca S Si	5.	2.	9.	13.	0.	20.	0.	0.	48.	1.	3.	0.	0.	0.	0.	8.8
60	Ca Si S	6.	2.	11.	19.	0.	15.	0.	0.	43.	1.	4.	0.	0.	0.	0.	5.6
9	Si Ca S	8.	0.	8.	45.	0.	13.	0.	1.	23.	0.	2.	0.	0.	0.	0.	0.9
6	Si Al S	3.	0.	28.	40.	0.	18.	0.	1.	9.	0.	2.	0.	1.	0.	0.	0.7
21	Ca S Na	14.	2.	7.	10.	0.	22.	0.	0.	42.	0.	2.	0.	0.	0.	0.	2.3
167	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																10.6

TABLE 4-48. - PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11,
impactors #1 + cup (Cont.)

.....
1191 TOTALS - 7. 2. 14. 25. 0. 8. 0. 0. 37. 1. 5. 1. 0. 0. 0. 100.0

SAMPLE # 564 PSI/ARIZONA ASH BEULAH 1.6KG/HR. 1160C PORT 11 IMP.#1 + CUP
NUMBER 564 DISK 42 FILE 105 - 108 PARTICLES
RUN 1 DATE 4-JAN-92 SUMMARY 108 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si - -	4.9	1.	15.	17.	55.	13.	0.	0.
Ca - -	6.4	3.	23.	17.	45.	12.	1.	0.
Ca Si Al	25.9	6.	29.	33.	26.	4.	2.	0.
Si Al Ca	5.4	7.	25.	12.	46.	8.	2.	0.
Si Al Na	8.6	14.	31.	24.	23.	7.	1.	0.
Ca S Si	8.8	6.	14.	36.	43.	1.	0.	0.
Ca Si S	5.6	3.	18.	38.	40.	1.	0.	0.
OTHERS -	34.4	8.	18.	30.	35.	7.	2.	0.
TOTALS -	100.0	7.	22.	29.	35.	6.	1.	0.

TABLE 4-49. - PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11,
impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 565 PSI/ARIZONA ASH BEULAH 1.6 KG/HR 1160C PORT 11 IMPS 2+3+4.

NUMBER 565 DISK 42 FILE 113 - 116 PARTICLES

RUN 1 DATE 6-JAN-92 SUMMARY 116 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>5000 0

TOTAL Volume FACTOR: 0.15303E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
3	Fe - -	0.	0.	1.	5.	0.	5.	0.	0.	1.	0.	88.	0.	0.	0.	0.	0.8
64	S Na -	38.	0.	1.	1.	0.	55.	0.	1.	4.	0.	0.	0.	0.	0.	0.	4.9
128	S Ca Na	18.	1.	8.	9.	0.	38.	0.	1.	23.	1.	2.	0.	0.	0.	0.	11.4
659	S Na Ca	27.	1.	5.	7.	0.	43.	0.	1.	15.	1.	1.	0.	0.	0.	0.	54.2
19	Ca S Na	19.	1.	10.	12.	0.	26.	0.	1.	28.	1.	2.	0.	0.	0.	0.	2.0
27	Na S Ca	37.	1.	5.	7.	0.	32.	0.	2.	14.	0.	1.	0.	0.	0.	0.	3.1
7	S K Ca	0.	0.	1.	5.	0.	53.	0.	32.	8.	0.	1.	0.	1.	0.	0.	0.6
40	S Ca Si	10.	1.	10.	14.	0.	36.	0.	2.	23.	1.	3.	0.	0.	0.	0.	3.3
32	Ca S Si	11.	2.	12.	17.	0.	23.	0.	1.	30.	1.	3.	0.	0.	0.	0.	3.1
49	S Na Mg	21.	9.	1.	3.	0.	61.	0.	0.	6.	0.	0.	0.	0.	0.	0.	1.9
3	Si*Al S	16.	0.	22.	28.	0.	19.	0.	0.	9.	3.	3.	0.	0.	0.	0.	0.6
2	Si S Al	14.	0.	19.	27.	0.	19.	0.	0.	18.	0.	2.	0.	0.	0.	0.	0.5
6	Si Al Na	23.	0.	28.	32.	0.	6.	0.	0.	8.	0.	2.	0.	0.	0.	0.	0.8
32	S Na Si	26.	0.	8.	14.	0.	38.	0.	1.	11.	0.	1.	0.	0.	0.	0.	2.6
3	S Si Na	20.	1.	17.	23.	0.	28.	0.	0.	10.	0.	0.	0.	0.	0.	0.	0.8
6	Si Al Ca	14.	0.	23.	27.	0.	13.	0.	1.	20.	0.	1.	0.	0.	0.	0.	0.5
4	Si Ca Al	16.	0.	19.	26.	0.	13.	0.	1.	23.	0.	3.	0.	0.	0.	0.	0.9
1	Ca Al Si	18.	0.	22.	20.	0.	13.	0.	0.	22.	0.	6.	0.	0.	0.	0.	0.5
5	S Ca Al	2.	0.	12.	6.	0.	56.	0.	0.	17.	6.	1.	0.	0.	0.	0.	0.6
5	S S K Na	16.	0.	1.	3.	0.	49.	0.	23.	7.	0.	0.	0.	1.	0.	0.	0.5
94	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.3
1192	TOTALS -	23.	1.	6.	9.	0.	39.	0.	2.	16.	1.	2.	0.	0.	0.	0.	100.0

TABLE 4-49. - PSIT/Arizona ash Beulah, 1.6 kg/h, 1160°C, port 11,
impactors 2+3+4 (Cont.)

SAMPLE # 565 PSI/ARIZONA ASH BEULAH 1.6 KG/HR 1160C PORT 11 IMPS 2+3+4.
NUMBER 565 DISK 42 FILE 113 - 116 PARTICLES
RUN 1 DATE 6-JAN-92 SUMMARY 116 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S Na -	4.9	1.	54.	25.	21.	0.	0.	0.
S Ca Na	11.4	50.	22.	14.	12.	3.	0.	0.
S Na Ca	54.2	55.	19.	17.	9.	0.	0.	0.
OTHERS -	29.6	62.	18.	13.	6.	1.	0.	0.
TOTALS -	100.0	54.	20.	16.	9.	1.	0.	0.

**TABLE 4-50. - PSIT/Arizona Beulah ash on filter, 1.6 kg/h, 1160°C,
port 11, impactors 5+6+7**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 566 PSI/ARIZONA BEULAH ASH ON FILTER 1.6KG/HR,1160C, PORT 11, IMPS, 5+6+7
NUMBER 566 DISK 48 FILE 127 - 130 PARTICLES
RUN 1 DATE 23-MAR-92 SUMMARY 130 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.52585E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
11	Na - -	91.	0.	0.	1.	0.	3.	1.	0.	3.	0.	0.	0.	0.	0.	0.	0.6
6	Si - -	1.	0.	0.	77.	0.	8.	0.	1.	5.	2.	6.	0.	0.	0.	0.	0.7
3	Fe - -	2.	0.	3.	5.	0.	2.	0.	0.	2.	0.	86.	0.	0.	0.	0.	0.6
9	Ca S -	2.	0.	1.	2.	0.	42.	0.	0.	53.	0.	0.	0.	0.	0.	0.	0.9
185	Ca S Si	10.	1.	11.	16.	0.	25.	0.	0.	32.	1.	3.	0.	0.	0.	0.	12.0
66	S Ca Si	11.	0.	10.	16.	0.	33.	0.	0.	26.	1.	3.	0.	0.	0.	0.	5.3
7	Si Ca S	8.	1.	14.	27.	0.	19.	0.	1.	22.	5.	4.	0.	0.	0.	0.	0.7
40	Ca Si S	9.	2.	14.	21.	0.	17.	0.	1.	33.	1.	2.	0.	0.	0.	0.	3.9
6	Si S Ca	8.	0.	4.	39.	0.	24.	0.	2.	16.	2.	5.	1.	0.	0.	0.	1.2
200	S Ca Na	19.	0.	7.	10.	0.	35.	0.	0.	26.	1.	2.	0.	0.	0.	0.	13.1
77	S Na Ca	28.	1.	6.	7.	0.	35.	0.	0.	20.	1.	2.	0.	0.	0.	0.	11.3
79	Ca S Na	16.	0.	8.	11.	0.	29.	0.	0.	32.	0.	2.	0.	0.	0.	0.	6.5
24	Na S Ca	35.	2.	6.	7.	0.	30.	0.	0.	18.	1.	1.	0.	0.	0.	0.	2.1
7	Ca Na S	20.	1.	15.	16.	0.	18.	0.	1.	25.	1.	1.	1.	0.	0.	0.	0.5
9	Si Al S	1.	0.	30.	40.	0.	15.	0.	1.	7.	4.	2.	0.	1.	0.	0.	1.0
119	Ca Si Al	5.	4.	18.	23.	0.	8.	0.	0.	37.	1.	4.	0.	0.	0.	0.	10.7
32	Si Al Ca	11.	1.	26.	33.	0.	5.	0.	0.	19.	1.	4.	0.	0.	0.	0.	3.4
33	Si Ca Al	9.	4.	21.	30.	0.	8.	0.	0.	24.	1.	3.	0.	0.	0.	0.	2.3
27	Ca Al Si	1.	4.	21.	18.	0.	7.	0.	1.	42.	1.	4.	0.	0.	0.	0.	2.3
10	Ca S Al	5.	1.	15.	12.	0.	21.	0.	0.	39.	2.	2.	0.	2.	0.	0.	0.7
58	Si Al Na	20.	0.	28.	34.	0.	5.	0.	0.	10.	0.	3.	0.	0.	0.	0.	7.3
16	Si Na Al	28.	0.	23.	36.	0.	4.	0.	0.	7.	0.	2.	0.	0.	0.	0.	2.7
7	Si Al Fe	3.	0.	26.	41.	0.	5.	0.	6.	5.	0.	13.	0.	0.	0.	0.	1.1
7	Ca Na Si	20.	4.	12.	19.	0.	16.	0.	0.	23.	2.	3.	0.	0.	0.	0.	0.6
7	Si Ca Na	17.	3.	13.	30.	0.	11.	0.	1.	22.	1.	3.	0.	0.	0.	0.	0.6
3	S Ca Mg	12.	19.	4.	7.	0.	26.	0.	0.	22.	1.	8.	0.	1.	0.	0.	0.6
3	Ca S Mg	7.	14.	6.	5.	0.	28.	0.	0.	32.	4.	4.	0.	0.	0.	0.	0.6
123	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.8
1175	TOTALS -	15.	2.	13.	18.	0.	22.	0.	0.	25.	1.	4.	0.	0.	0.	0.	100.0

TABLE 4-50. - PSIT/Arizona Beulah ash on filter. 1.6 kg/h. 1160°C.
port 11. impactors 5+6+7 (Cont.)

SAMPLE 566 PSI/ARIZONA BEULAH ASH ON FILTER 1.6KG/HR,1160C, PORT 11, IMPS, 5+6+7
 NUMBER 566 DISK 48 FILE 127 - 130 PARTICLES
 RUN 1 DATE 23-MAR-92 SUMMARY 130 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca S Si	12.0	9.	14.	51.	25.	1.	0.	0.
S Ca Si	5.3	23.	15.	32.	28.	2.	0.	0.
S Ca Na	13.1	16.	22.	50.	12.	0.	0.	0.
S Na Ca	11.3	49.	43.	8.	0.	0.	0.	0.
Ca S Na	6.5	9.	35.	45.	10.	0.	0.	0.
Ca S Al	10.7	52.	31.	16.	1.	0.	0.	0.
Si Al Na	7.3	64.	26.	11.	0.	0.	0.	0.
OTHERS -	33.8	57.	17.	18.	6.	1.	0.	0.
TOTALS -	100.0	40.	23.	27.	9.	1.	0.	0.

**TABLE 4-51. - PSIT/Arizona Beulah ash on filter, Sample D,
1.6 kg/h, 1160°C, port 5 IM**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 567 PSI/UA BEULAH ASH ON FILTER SAMPLE D 1.6KG/HR 1160KG/HR PORT 5 IM
 NUMBER 567 DISK 52 FILE 121 - 124 PARTICLES
 RUN 1 DATE 21-APR-92 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.32698E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
42	Ca - -	0.	3.	4.	5.	0.	5.	0.	0.	79.	0.	3.	0.	0.	0.	0.	3.5
40	Si - -	4.	0.	1.	89.	0.	1.	0.	1.	3.	0.	0.	0.	0.	0.	0.	3.9
14	Fe - -	0.	0.	0.	3.	0.	0.	0.	0.	3.	0.	94.	0.	0.	0.	0.	1.0
4	Na - -	95.	0.	0.	0.	0.	1.	0.	0.	4.	0.	0.	0.	0.	0.	0.	0.8
22	Ca S -	1.	1.	3.	3.	0.	21.	0.	0.	69.	1.	1.	0.	0.	0.	0.	1.0
10	S Ca -	0.	1.	1.	1.	0.	64.	1.	0.	32.	0.	1.	0.	0.	0.	0.	1.0
4	Ca Fe -	0.	2.	2.	2.	0.	1.	0.	0.	58.	0.	35.	0.	0.	0.	0.	0.5
302	Ca Si Al	4.	3.	16.	22.	0.	4.	0.	0.	45.	2.	3.	0.	0.	0.	0.	26.3
38	Si Ca Al	12.	0.	21.	33.	0.	4.	0.	0.	26.	2.	3.	0.	0.	0.	0.	3.0
32	Si Al Ca	13.	0.	26.	33.	0.	3.	0.	0.	20.	1.	2.	0.	0.	0.	0.	2.6
39	Ca Al Si	2.	4.	19.	16.	0.	6.	0.	0.	49.	1.	3.	0.	0.	0.	0.	3.2
9	Ca Fe Si	0.	6.	9.	14.	0.	2.	0.	0.	53.	0.	16.	0.	0.	0.	0.	1.2
110	Si Al Na	24.	0.	28.	35.	0.	2.	0.	0.	10.	0.	1.	0.	0.	0.	0.	8.1
34	Si Na Al	30.	0.	25.	36.	0.	1.	0.	0.	5.	0.	2.	0.	0.	0.	0.	3.6
25	Na Si Al	33.	0.	24.	29.	0.	2.	0.	0.	9.	0.	2.	0.	0.	0.	0.	2.2
10	Ca Mg Si	0.	17.	7.	9.	0.	3.	0.	0.	60.	0.	3.	0.	0.	0.	0.	1.2
18	S Ca Na	19.	3.	2.	4.	0.	42.	0.	0.	28.	1.	1.	0.	0.	0.	0.	1.0
19	S Na Ca	28.	1.	3.	4.	0.	43.	0.	0.	18.	0.	0.	0.	2.	0.	0.	1.7
19	Ca S Na	16.	3.	8.	10.	0.	23.	0.	0.	36.	1.	3.	0.	0.	0.	0.	1.3
16	Ca Na S	22.	2.	9.	15.	0.	18.	0.	0.	31.	1.	2.	0.	0.	0.	0.	2.0
18	Ca S Mg	0.	11.	4.	5.	0.	16.	0.	0.	62.	0.	1.	1.	0.	0.	0.	1.7
10	Ca Mg S	0.	18.	9.	8.	0.	15.	0.	0.	43.	1.	5.	0.	0.	0.	0.	1.1
16	Si Ca Na	18.	1.	8.	43.	0.	3.	0.	0.	25.	1.	2.	0.	0.	0.	0.	1.6
14	Si Na Ca	19.	0.	7.	59.	0.	1.	0.	0.	12.	1.	1.	0.	0.	0.	0.	1.1
21	Ca Si Na	17.	1.	13.	21.	0.	10.	0.	0.	33.	1.	4.	0.	0.	0.	0.	1.9
9	Ca Na Si	20.	2.	15.	18.	0.	10.	0.	0.	32.	1.	3.	0.	0.	0.	0.	0.7
59	Ca S Si	6.	2.	9.	13.	0.	19.	0.	0.	47.	1.	3.	0.	0.	0.	0.	5.8
15	S Ca Si	0.	1.	3.	14.	0.	52.	0.	0.	27.	0.	1.	0.	1.	0.	0.	1.7
30	Ca Si S	6.	2.	11.	18.	0.	14.	0.	0.	46.	1.	3.	0.	0.	0.	0.	4.1
9	Si Ca S	8.	0.	5.	48.	0.	14.	0.	1.	22.	0.	1.	0.	0.	0.	0.	0.7
15	Ca S Al	5.	2.	13.	8.	0.	19.	0.	1.	47.	2.	2.	1.	0.	0.	0.	0.6
9	Ca Mg Al	0.	19.	11.	5.	0.	3.	0.	1.	52.	2.	6.	0.	1.	0.	0.	0.5

**TABLE 4-51. - PSIT/Arizona Beulah ash on filter, Sample D.
1.6 kg/h, 1160°C, port 5 IM (Cont.)**

9	Si Al Fe	0.	0.	32.	45.	0.	3.	0.	5.	3.	0.	11.	0.	0.	0.	0.	0.5
4	Fe Si Al	4.	0.	13.	27.	0.	1.	0.	4.	4.	0.	47.	0.	0.	0.	0.	0.5
7	OTHERS -	15.	0.	11.	30.	0.	11.	0.	0.	9.	4.	19.	0.	0.	0.	0.	0.9
133	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																7.3
1185	TOTALS -	10.	2.	14.	24.	0.	9.	0.	0.	34.	1.	4.	0.	0.	0.	0.	100.0

SAMPLE 567 PSI/UA BEULAH ASH ON FILTER SAMPLE D 1.6KG/HR 1160KG/HR PORT 5 IM
NUMBER 567 DISK 52 FILE 121 - 124 PARTICLES
RUN 1 DATE 21-APR-92 SUMMARY 124 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca Si Al	26.3	10.	35.	40.	14.	1.	0.	0.
Si Al Na	8.1	16.	39.	27.	12.	6.	0.	0.
Ca S Si	5.8	4.	49.	38.	7.	2.	0.	0.
Ca Si S	4.1	2.	66.	32.	0.	0.	0.	0.
OTHERS -	55.8	11.	30.	27.	26.	4.	1.	0.
TOTALS -	100.0	11.	34.	32.	20.	3.	0.	0.

TABLE 4-52. - PSIT/Arizona Beulah ash 1.6 kg/h. port 5. impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 568 PSI/ARIZONA BEULAH ASH 1.6KG/HR 1160C PORT 5 IMPS. 2+3+4.
 NUMBER 568 DISK 42 FILE 133 - 136 PARTICLES
 RUN 1 DATE 21-JAN-92 SUMMARY 136 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.13009E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
13	Si - -	1.	0.	2.	94.	0.	1.	0.	2.	0.	0.	0.	0.	0.	0.	0.	1.6
2	Ca - -	0.	7.	7.	6.	0.	6.	0.	0.	69.	0.	6.	0.	0.	0.	0.	0.7
19	Ca S Al	1.	1.	16.	10.	0.	24.	1.	1.	42.	1.	3.	0.	0.	0.	0.	1.7
26	S Ca Si	1.	2.	4.	13.	0.	44.	1.	0.	32.	2.	2.	0.	0.	0.	0.	3.6
87	Ca S Si	5.	2.	10.	15.	0.	24.	0.	1.	40.	1.	3.	0.	0.	0.	0.	6.4
52	Ca Si S	4.	2.	14.	21.	0.	16.	0.	0.	36.	4.	2.	0.	0.	0.	0.	4.1
7	Si Ca S	3.	4.	9.	39.	0.	13.	0.	0.	24.	0.	8.	0.	0.	0.	0.	0.8
448	Ca Si Al	6.	4.	18.	23.	0.	6.	0.	0.	39.	1.	4.	0.	0.	0.	0.	34.7
40	Ca Al Si	3.	6.	19.	16.	0.	4.	0.	0.	46.	2.	4.	0.	0.	0.	0.	3.6
50	Si Ca Al	9.	2.	21.	31.	0.	5.	0.	0.	27.	1.	4.	0.	0.	0.	0.	3.3
47	Si Al Ca	12.	1.	26.	32.	0.	4.	0.	0.	20.	1.	2.	0.	0.	0.	0.	5.7
29	Ca S Na	17.	4.	9.	12.	0.	24.	0.	0.	30.	2.	2.	0.	0.	0.	0.	3.1
13	S Ca Na	18.	1.	7.	10.	0.	33.	0.	0.	28.	0.	3.	0.	0.	0.	0.	0.5
10	Ca Si Mg	2.	15.	12.	20.	0.	9.	0.	0.	36.	0.	5.	0.	0.	0.	0.	0.9
23	Ca Si Na	20.	1.	16.	24.	0.	7.	0.	0.	27.	2.	2.	0.	0.	0.	0.	2.4
10	Si Ca Na	19.	1.	12.	34.	0.	5.	0.	0.	24.	1.	4.	0.	0.	0.	0.	0.6
10	Si Na Ca	18.	1.	9.	46.	0.	5.	0.	1.	14.	2.	4.	0.	0.	0.	0.	0.8
4	Ca S Fe	0.	1.	6.	1.	0.	31.	0.	1.	48.	0.	11.	0.	0.	0.	0.	0.5
36	Si Na Al	29.	0.	22.	35.	0.	2.	0.	0.	8.	1.	2.	0.	0.	0.	0.	3.4
70	Si Al Na	22.	0.	28.	34.	0.	2.	0.	0.	11.	0.	2.	0.	0.	0.	0.	8.3
9	Na Si Al	35.	0.	24.	31.	0.	1.	0.	1.	6.	1.	1.	0.	0.	0.	0.	1.0
3	S Si Al	0.	0.	23.	29.	0.	34.	0.	0.	11.	0.	2.	2.	0.	0.	0.	0.6
3	Ca S K	0.	9.	5.	2.	0.	21.	0.	12.	44.	1.	0.	0.	4.	0.	0.	0.6
3	Si Al K	0.	0.	35.	55.	0.	2.	0.	8.	0.	0.	1.	0.	0.	0.	0.	0.5
7	OTHERS -	3.	8.	9.	12.	0.	13.	0.	1.	27.	13.	12.	2.	0.	0.	0.	0.5
154	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.9
1175	TOTALS -	8.	3.	17.	24.	0.	11.	0.	1.	31.	1.	4.	0.	0.	0.	0.	100.0

**TABLE 4-52. - PSIT/Arizona Beulah ash 1.6 kg/h. port 5.
impactors 2+3+4 (Cont.)**

SAMPLE # 568 PSI/ARIZONA BEULAH ASH 1.6KG/HR 1160C PORT 5 IMPS. 2+3+4.

NUMBER 568 DISK 42 FILE 133 - 136 PARTICLES

RUN 1 DATE 21-JAN-92 SUMMARY 136 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca S Si	6.4	2.	22.	46.	27.	1.	2.	0.
Ca Si S	4.1	9.	35.	43.	13.	0.	0.	0.
Ca Si Al	34.7	24.	37.	32.	6.	0.	1.	0.
Si Al Ca	5.7	18.	68.	13.	2.	0.	0.	0.
Si Al Na	8.3	42.	50.	8.	0.	0.	0.	0.
OTHERS -	41.0	31.	36.	23.	8.	2.	0.	0.
TOTALS -	100.0	26.	38.	27.	8.	1.	0.	0.

**TABLE 4-53. - PSIT/Arizona Beulah ash, 2.9 kg/h, 1245°C,
port 11, impactors #1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 570 PS/ARIZONA BEULAH ASH 2.9 KG/HR 1245C PORT 11 IMP #1 + CUP.

NUMBER 570 DISK 42 FILE 117 - 120 PARTICLES
RUN 1 DATE 7-JAN-92 SUMMARY 120 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.31707E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
46	Si - -	3.	0.	0.	93.	0.	1.	0.	1.	2.	0.	0.	0.	0.	0.	0.	3.0
16	Fe - -	0.	0.	2.	4.	0.	0.	0.	0.	4.	0.	89.	0.	0.	0.	0.	1.6
25	Ca - -	0.	4.	6.	6.	0.	7.	0.	0.	73.	1.	3.	0.	0.	0.	0.	2.3
31	Ca S -	1.	0.	1.	3.	0.	19.	0.	0.	75.	0.	1.	0.	0.	0.	0.	2.2
4	Si Na -	17.	0.	0.	81.	0.	1.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.5
4	Si Al -	0.	0.	34.	53.	0.	1.	0.	5.	3.	1.	4.	0.	0.	0.	0.	0.9
306	Ca Si Al	3.	4.	17.	22.	0.	4.	0.	0.	46.	1.	3.	0.	0.	0.	0.	26.4
70	Si Al Ca	11.	0.	28.	35.	0.	3.	0.	0.	21.	1.	2.	0.	0.	0.	0.	6.7
42	Ca Al Si	1.	5.	20.	15.	0.	2.	0.	0.	52.	2.	3.	0.	0.	0.	0.	3.2
46	Si Ca Al	10.	1.	21.	33.	0.	6.	0.	0.	26.	1.	2.	0.	0.	0.	0.	3.2
162	Si Al Na	22.	0.	30.	37.	0.	1.	0.	0.	7.	0.	1.	0.	0.	0.	0.	13.4
14	Si Na Al	27.	0.	24.	40.	0.	3.	0.	0.	6.	0.	0.	0.	0.	0.	0.	1.8
14	Si Ca Na	14.	0.	6.	51.	0.	4.	0.	0.	23.	1.	1.	0.	0.	0.	0.	0.9
8	Ca Si Na	20.	1.	18.	24.	0.	6.	0.	0.	29.	1.	1.	0.	0.	0.	0.	0.8
10	Si Na Ca	18.	0.	2.	66.	0.	0.	0.	0.	11.	0.	1.	0.	0.	0.	0.	0.8
81	Ca S Si	6.	2.	8.	13.	0.	18.	0.	0.	49.	1.	3.	0.	0.	0.	0.	6.8
10	Si Ca S	5.	0.	7.	36.	0.	18.	0.	3.	26.	0.	5.	0.	0.	0.	0.	1.0
33	Ca Si S	6.	3.	11.	19.	0.	15.	0.	0.	42.	2.	2.	0.	0.	0.	0.	2.7
23	Ca Mg Si	0.	23.	8.	14.	0.	4.	0.	1.	46.	0.	5.	0.	0.	0.	0.	2.9
15	Ca Mg Al	0.	19.	13.	9.	0.	4.	0.	0.	49.	0.	6.	0.	0.	0.	0.	1.0
13	Ca Al Mg	0.	14.	17.	5.	0.	3.	0.	0.	55.	0.	5.	0.	0.	0.	0.	1.0
14	Ca S Al	1.	5.	12.	6.	0.	19.	0.	1.	51.	0.	4.	0.	1.	0.	0.	0.8
25	S Ca Na	19.	0.	3.	5.	0.	42.	0.	0.	30.	0.	0.	0.	0.	0.	0.	2.6
17	Ca S Na	15.	1.	7.	9.	0.	27.	0.	0.	40.	1.	1.	0.	0.	0.	0.	2.6
7	S Na Ca	27.	0.	3.	5.	0.	40.	0.	1.	24.	0.	0.	0.	0.	0.	0.	0.7
3	Ca Si Ti	1.	0.	12.	19.	0.	2.	0.	0.	49.	1.	3.	0.	0.	0.	0.	0.5
17	Ca S Mg	0.	10.	4.	4.	0.	16.	0.	0.	63.	0.	2.	0.	0.	0.	0.	1.2
131	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.2
1188	TOTALS -	8.	3.	16.	25.	0.	8.	0.	0.	34.	1.	4.	0.	0.	0.	0.	100.0

**TABLE 4-53. - PSIT/Arizona Beulah ash, 2.9 kg/h, 1245°C,
port 11, impactors #1 + cup (Cont.)**

SAMPLE # 570 PSI/ARIZONA ASH 2.9 KG/HR 1245C PORT 11 IMP #1 + CUP.
 NUMBER 570 DISK 42 FILE 117 - 120 PARTICLES
 RUN 1 DATE 7-JAN-92 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca Si Al	26.4	18.	34.	30.	16.	1.	0.	0.
Si Al Ca	6.7	13.	49.	23.	13.	3.	0.	0.
Si Al Na	13.4	28.	30.	22.	16.	3.	0.	0.
Ca S Si	6.8	12.	16.	45.	26.	0.	1.	0.
OTHERS -	46.7	19.	30.	28.	21.	2.	0.	0.
TOTALS -	100.0	19.	31.	28.	19.	2.	0.	0.

TABLE 4-54. - PSIT/Arizona ash Beulah, 2.9 kg/h. 1245°C.
port 11, impactors 2+3+4

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 571 PSI/ARIZONA ASH BEULAH 2.9KG/MR 1245C PORT 11 IMPS 2+3+4.
 NUMBER 571 DISK 40 FILE 129 - 132 PARTICLES
 RUN 1 DATE 30-DEC-91 SUMMARY 132 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>5000 0

TOTAL Volume FACTOR: 0.12273E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
5	Ca S	-	0.	1.	1.	3.	0.	33.	0.	0.	61.	0.	0.	0.	0.	0.	0.5
72	S Ca Si	10.	0.	11.	16.	0.	34.	0.	0.	28.	1.	1.	0.	0.	0.	0.	4.9
178	Ca S Si	8.	1.	11.	16.	0.	25.	0.	0.	33.	1.	3.	0.	0.	0.	0.	11.8
11	Si Ca S	11.	2.	9.	41.	0.	15.	0.	1.	18.	1.	2.	0.	1.	0.	0.	0.5
27	Ca Si S	9.	0.	13.	25.	0.	18.	0.	0.	30.	1.	2.	0.	1.	0.	0.	2.5
6	Si S Ca	4.	0.	11.	37.	0.	20.	0.	0.	17.	6.	0.	4.	0.	0.	0.	0.5
135	Ca Si Al	2.	6.	19.	24.	0.	5.	0.	0.	39.	1.	4.	0.	0.	0.	0.	12.1
12	Ca Al Si	0.	10.	20.	17.	0.	3.	0.	0.	44.	0.	5.	0.	0.	0.	0.	1.0
66	Si Al Ca	8.	1.	27.	36.	0.	4.	0.	0.	19.	2.	3.	0.	0.	0.	0.	6.8
37	Si Ca Al	10.	2.	21.	30.	0.	7.	0.	0.	26.	1.	4.	0.	0.	0.	0.	6.0
344	S Ca Na	18.	0.	5.	7.	0.	39.	0.	0.	29.	0.	1.	0.	0.	0.	0.	18.2
16	S Na Ca	26.	0.	5.	7.	0.	38.	0.	0.	23.	0.	0.	0.	0.	0.	0.	3.9
49	Ca S Na	14.	3.	9.	11.	0.	29.	0.	0.	31.	1.	3.	0.	0.	0.	0.	2.2
5	Na S Ca	26.	2.	13.	14.	0.	24.	0.	0.	19.	0.	3.	0.	0.	0.	0.	0.9
65	Si Al Na	20.	0.	29.	37.	0.	3.	0.	0.	9.	1.	2.	0.	0.	0.	0.	8.1
17	Si Na Al	28.	0.	25.	31.	0.	6.	0.	0.	7.	1.	1.	0.	0.	0.	0.	2.8
16	Ca S Al	7.	2.	12.	10.	0.	28.	0.	0.	37.	1.	2.	0.	0.	0.	0.	1.2
6	Si Ca Na	18.	0.	4.	39.	0.	13.	0.	0.	25.	0.	0.	0.	0.	0.	0.	1.6
5	Si Al S	14.	0.	20.	30.	0.	17.	0.	2.	15.	0.	2.	0.	0.	0.	0.	1.9
6	Ca Mg Si	0.	18.	9.	11.	0.	5.	0.	0.	47.	1.	8.	0.	0.	0.	0.	1.2
5	Ca Al Mg	0.	22.	26.	5.	0.	1.	0.	0.	40.	0.	5.	0.	0.	0.	0.	0.7
4	Ca Mg Al	0.	25.	13.	9.	0.	5.	0.	0.	40.	0.	8.	0.	0.	0.	0.	1.5
1	Ca Ti Si	0.	5.	14.	17.	0.	4.	0.	0.	38.	20.	3.	0.	0.	0.	0.	1.2
1	Si Al K	0.	0.	30.	54.	0.	0.	0.	9.	0.	0.	7.	0.	0.	0.	0.	1.0
101	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.7
1191	TOTALS	-	11.	3.	15.	21.	0.	19.	0.	0.	27.	1.	3.	0.	0.	0.	100.0

**TABLE 4-54. - PSIT/Arizona ash Beulah, 2.9 kg/h. 1245°C.
port 11, impactors 2+3+4 (Cont.)**

SAMPLE # 571 PSI/ARIZONA ASH BEULAH 2.9KG/HR 1245C PORT 11 IMPS 2+3+4.
NUMBER 571 DISK 40 FILE 129 - 132 PARTICLES
RUN 1 DATE 30-DEC-91 SUMMARY 132 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S Ca Si	4.9	9.	45.	35.	10.	1.	0.	0.
Ca S Si	11.8	9.	34.	35.	21.	1.	0.	0.
Ca Si Al	12.1	82.	8.	8.	1.	0.	0.	0.
Si Al Ca	6.8	84.	13.	3.	0.	0.	0.	0.
Si Ca Al	6.0	44.	50.	5.	0.	0.	0.	0.
S Ca Na	18.2	13.	35.	48.	4.	0.	0.	0.
Si Al Na	8.1	81.	13.	6.	0.	0.	0.	0.
OTHERS -	32.2	43.	41.	12.	3.	0.	0.	0.
TOTALS -	100.0	43.	32.	21.	5.	0.	0.	0.

**TABLE 4-55. - PSIT/Arizona Beulah ash on filter, 2.9 kg/h,
1245°C, port 11, impactors 5+6**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 572 PSI/ARIZONA BEULAH ASH ON FILTER 2.9KG/HR, 1245C, PORT 11, IMPS, 5+6+
NUMBER 572 DISK 48 FILE 131 - 134 PARTICLES
RUN 1 DATE 25-MAR-92 SUMMARY 134 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.27503E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
236	S Ca Na	19.	1.	7.	9.	0.	35.	0.	0.	25.	1.	2.	0.	0.	0.	0.	9.9
366	S Na Ca	28.	1.	5.	7.	0.	38.	0.	1.	18.	0.	2.	0.	0.	0.	0.	31.5
46	Ca S Na	16.	2.	9.	12.	0.	23.	0.	0.	34.	1.	4.	0.	0.	0.	0.	4.1
10	Ca Na S	22.	1.	12.	14.	0.	18.	0.	0.	28.	0.	4.	0.	0.	0.	0.	1.2
93	Na S Ca	37.	0.	5.	8.	0.	30.	0.	0.	16.	1.	2.	0.	0.	0.	0.	14.4
76	S Ca Si	1.	0.	8.	16.	0.	43.	0.	0.	28.	0.	2.	0.	0.	0.	0.	4.8
58	Ca S Si	1.	4.	15.	20.	0.	23.	0.	0.	31.	1.	4.	0.	0.	0.	0.	4.5
11	Ca Si S	7.	0.	14.	20.	0.	16.	0.	0.	34.	3.	5.	0.	1.	0.	0.	0.8
17	Na S Si	28.	0.	12.	19.	0.	22.	0.	0.	14.	0.	4.	0.	0.	0.	0.	3.1
6	S Na Si	21.	0.	10.	18.	0.	28.	7.	0.	15.	0.	0.	0.	0.	0.	0.	0.6
4	Si Na S	15.	0.	1.	61.	0.	10.	0.	4.	7.	0.	2.	0.	0.	0.	0.	0.5
16	S Ca Al	0.	0.	15.	10.	0.	45.	1.	0.	24.	0.	3.	0.	1.	0.	0.	1.5
14	Si Ca Al	5.	5.	20.	30.	0.	8.	0.	1.	25.	2.	3.	0.	0.	0.	0.	0.9
29	Ca Si Al	5.	3.	19.	22.	0.	11.	0.	0.	34.	2.	3.	0.	0.	0.	0.	4.1
4	Ca Al Si	4.	5.	21.	16.	0.	8.	0.	0.	42.	0.	4.	0.	0.	0.	0.	0.5
15	Si Al Ca	7.	1.	28.	34.	0.	7.	0.	0.	18.	1.	3.	0.	0.	0.	0.	2.7
7	Si Na Ca	21.	0.	14.	29.	0.	14.	0.	0.	17.	2.	3.	0.	0.	0.	0.	1.6
5	Ca Si Na	17.	4.	13.	19.	0.	13.	0.	0.	29.	2.	3.	0.	0.	0.	0.	0.6
25	Si Al Na	21.	0.	30.	36.	0.	3.	0.	0.	7.	1.	2.	0.	0.	0.	0.	2.9
7	Na Si Al	29.	0.	22.	26.	0.	9.	0.	1.	9.	1.	2.	0.	0.	0.	0.	1.1
5	Si Na Al	27.	0.	22.	31.	0.	7.	0.	0.	10.	1.	0.	0.	0.	0.	0.	0.6
8	Si Al S	0.	0.	32.	39.	0.	15.	0.	1.	10.	1.	0.	0.	2.	0.	0.	0.7
1	Mg Ca S	0.	31.	8.	7.	0.	16.	0.	0.	28.	0.	9.	0.	0.	0.	0.	0.5
2	S Ca Ti	0.	0.	0.	3.	0.	62.	0.	0.	24.	7.	4.	0.	0.	0.	0.	0.6
1	Si Al Ti	9.	0.	20.	32.	0.	9.	0.	0.	9.	16.	4.	0.	0.	0.	0.	0.8
113	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																5.0
1175	TOTALS -	21.	1.	10.	14.	0.	29.	0.	0.	21.	1.	3.	0.	0.	0.	0.	100.0

**TABLE 4-55. - PSIT/Arizona Beulah ash on filter, 2.9 kg/h,
1245°C, port 11, impactors 5+6 (Cont.)**

SAMPLE 572 PSI/ARIZONA BEULAH ASH ON FILTER 2.9KG/HR, 1245C, PORT 11, IMPS, 5+6+
 NUMBER 572 DISK 48 FILE 131 - 134 PARTICLES
 RUN 1 DATE 25-MAR-92 SUMMARY 134 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S Ca Na	9.9	32.	35.	19.	11.	2.	1.	0.
S Na Ca	31.5	53.	37.	8.	2.	0.	0.	0.
Ca S Na	4.1	30.	60.	10.	1.	0.	0.	0.
Na S Ca	14.4	66.	32.	2.	0.	0.	0.	0.
S Ca Si	4.8	59.	22.	8.	3.	5.	2.	0.
Ca S Si	4.5	29.	58.	8.	3.	1.	0.	0.
Ca Si Al	4.1	80.	17.	2.	1.	0.	0.	0.
OTHERS -	26.8	71.	23.	4.	1.	1.	0.	0.
TOTALS -	100.0	57.	32.	7.	2.	1.	0.	0.

TABLE 4-56. - PSIT/SECV Beulah ash probe (combustion chamber) on filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE #596 PSI Beulah ash probe (comb. chamber) on filter
 NUMBER 596 DISK 53 FILE 113 - 116 PARTICLES
 RUN 1 DATE 25-JUL-91 SUMMARY 116 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.11368E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
51	Ca - -	0.	4.	2.	3.	0.	4.	0.	0.	83.	0.	3.	0.	0.	0.	0.	3.8
54	Fe - -	0.	1.	0.	2.	0.	1.	0.	0.	2.	1.	93.	0.	0.	0.	0.	5.1
29	Si - -	3.	0.	0.	95.	0.	1.	0.	0.	0.	0.	0.	0.	0.	0.	0.	1.7
64	Ca S -	0.	1.	0.	1.	0.	33.	0.	0.	65.	0.	0.	0.	0.	0.	0.	5.0
21	Si Al -	0.	0.	43.	54.	0.	0.	0.	0.	1.	0.	0.	0.	1.	0.	0.	1.8
19	Si Na -	27.	0.	0.	66.	0.	2.	0.	0.	3.	1.	1.	1.	0.	0.	0.	1.5
6	Ca Mg -	0.	14.	3.	0.	0.	4.	0.	0.	76.	0.	4.	0.	0.	0.	0.	0.9
10	Fe Ca -	0.	2.	1.	2.	0.	3.	0.	0.	19.	0.	73.	0.	0.	0.	0.	1.3
141	Si Al Na	22.	0.	32.	40.	0.	1.	0.	0.	4.	0.	1.	0.	0.	0.	0.	11.5
9	Al Si Na	20.	0.	38.	36.	0.	0.	0.	0.	3.	1.	1.	0.	0.	0.	0.	0.7
96	Si Na Al	31.	0.	24.	37.	0.	1.	0.	0.	4.	0.	2.	0.	0.	0.	0.	7.5
53	Na Si Al	38.	0.	22.	30.	0.	3.	0.	0.	3.	1.	2.	0.	0.	0.	0.	4.7
61	Ca Si Al	2.	1.	18.	22.	0.	4.	0.	0.	44.	1.	7.	0.	1.	0.	0.	5.2
13	Si Ca Al	5.	0.	20.	35.	0.	2.	0.	0.	29.	2.	6.	0.	0.	0.	0.	1.1
34	Si Al Ca	1.	0.	34.	45.	0.	1.	0.	0.	17.	1.	1.	0.	0.	0.	0.	3.0
19	Ca Al Si	0.	6.	18.	14.	0.	5.	0.	0.	51.	0.	5.	0.	0.	0.	0.	1.3
26	Ca S Si	3.	3.	9.	13.	0.	20.	0.	0.	45.	1.	6.	0.	0.	0.	0.	1.5
12	S Ca Si	1.	0.	7.	19.	0.	33.	0.	1.	26.	0.	11.	0.	0.	0.	0.	0.5
7	Ca Si S	0.	2.	14.	19.	0.	16.	0.	0.	44.	0.	5.	0.	0.	0.	0.	0.9
9	Ca Mg Al	0.	16.	9.	5.	0.	3.	0.	0.	61.	1.	4.	0.	1.	0.	0.	0.5
16	Fe Ca Si	0.	0.	10.	17.	0.	8.	0.	0.	21.	1.	43.	0.	0.	0.	0.	1.2
10	Ca Si Fe	2.	4.	10.	19.	0.	2.	0.	0.	45.	2.	16.	0.	0.	0.	0.	0.9
6	Si Al Fe	11.	0.	27.	40.	0.	1.	1.	0.	4.	1.	14.	0.	0.	0.	0.	0.5
16	S Ca Na	16.	0.	2.	2.	0.	42.	0.	0.	33.	0.	3.	0.	1.	0.	0.	2.5
14	S Na Ca	27.	1.	8.	8.	0.	31.	0.	0.	19.	0.	7.	0.	0.	0.	0.	1.6
22	Ca S Na	15.	2.	5.	7.	0.	26.	0.	0.	35.	1.	7.	0.	0.	0.	0.	2.4
8	Na S Ca	35.	0.	5.	9.	0.	24.	0.	2.	16.	2.	6.	0.	1.	0.	0.	0.9
35	Ca S Fe	3.	2.	5.	5.	0.	25.	0.	0.	44.	2.	14.	0.	0.	0.	0.	2.8
14	Fe Ca S	3.	1.	5.	8.	0.	13.	0.	0.	19.	0.	50.	0.	0.	0.	0.	0.8
6	S Fe Ca	2.	0.	8.	11.	0.	30.	0.	0.	21.	2.	25.	0.	0.	0.	0.	0.5
10	Ca Fe S	1.	4.	9.	6.	0.	14.	0.	0.	39.	1.	26.	0.	0.	0.	0.	1.0
14	S Ca Fe	1.	4.	2.	6.	0.	38.	0.	0.	33.	2.	14.	0.	0.	0.	0.	1.7

TABLE 4-56. - PSIT/SECV Beulah ash probe (combustion chamber) on filter (Cont.)

8	Ca Mg Fe	0.	20.	3.	1.	0.	2.	0.	0.	58.	0.	16.	0.	1.	0.	0.	0.7
6	Ca Fe Mg	0.	9.	6.	5.	0.	7.	0.	0.	50.	0.	23.	0.	0.	0.	0.	0.7
9	Ca S Al	5.	3.	14.	9.	0.	20.	0.	0.	39.	1.	8.	0.	1.	0.	0.	0.8
8	Ca Fe Al	0.	5.	13.	7.	0.	5.	0.	0.	46.	0.	23.	0.	0.	0.	0.	0.6
4	Ti S Si	0.	0.	8.	19.	0.	34.	0.	0.	0.	38.	0.	0.	0.	0.	0.	0.7
6	Si Na Ca	24.	0.	5.	42.	0.	7.	0.	0.	14.	0.	8.	0.	0.	0.	0.	0.5
4	Ca Si Na	14.	2.	12.	26.	0.	3.	0.	0.	36.	1.	6.	0.	0.	0.	0.	0.6
30	Ca S Mg	0.	10.	2.	2.	0.	25.	0.	0.	57.	0.	3.	0.	0.	0.	0.	2.3
13	Ca Mg S	0.	14.	5.	5.	0.	9.	0.	0.	62.	0.	5.	0.	0.	0.	0.	0.7
3	Fe Na Si	17.	0.	14.	16.	0.	5.	0.	0.	8.	0.	40.	0.	0.	0.	0.	0.6
4	Si Al S	0.	0.	31.	37.	0.	17.	0.	0.	3.	10.	1.	0.	1.	0.	0.	0.5
50	OTHERS -	3.	5.	14.	17.	1.	18.	1.	1.	17.	9.	14.	0.	0.	0.	0.	6.6
49	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.0
99	TOTALS -	10.	2.	14.	22.	0.	11.	0.	0.	26.	2.	13.	0.	0.	0.	0.	100.0

SAMPLE #596 PSI Beulah ash probe (comb. chamber) on filter
NUMBER 596 DISK 53 FILE 113 - 116 PARTICLES
RUN 1 DATE 25-JUL-91 SUMMARY 116 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Fe - -	5.1	11.	64.	17.	7.	2.	0.	0.
Ca S -	5.0	2.	19.	23.	43.	14.	0.	0.
Si Al Na	11.5	18.	40.	20.	17.	5.	0.	0.
Si Na Al	7.5	49.	31.	14.	7.	0.	0.	0.
Na Si Al	4.7	57.	39.	4.	0.	0.	0.	0.
Ca Si Al	5.2	10.	57.	21.	7.	7.	0.	0.
OTHERS -	6.6	34.	65.	1.	0.	0.	0.	0.
OTHERS -	54.3	13.	40.	24.	20.	3.	0.	0.
TOTALS -	100.0	19.	42.	20.	16.	4.	0.	0.

TABLE 4-57. - PSIT/SECV Beulah ash probe (horiz. duct.) on filter

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 597 PSI Beulah ash probe (horiz. duct.) on filter

NUMBER 597 DISK 53 FILE 117 - 120 PARTICLES
 RUN 1 DATE 26-JUL-91 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

.TOTAL Volume FACTOR: 0.17002E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
33	Ca - -	0.	4.	3.	2.	0.	6.	0.	0.	83.	1.	2.	0.	0.	0.	0.	3.6
22	Si - -	5.	0.	0.	94.	0.	0.	0.	0.	0.	0.	1.	0.	0.	0.	0.	1.7
39	Fe - -	0.	0.	1.	2.	0.	3.	0.	0.	3.	0.	91.	0.	0.	0.	0.	2.6
57	Ca S -	0.	0.	0.	0.	0.	25.	0.	0.	74.	0.	0.	0.	0.	0.	0.	4.6
15	Si Al -	0.	0.	41.	57.	0.	0.	0.	0.	1.	1.	0.	0.	0.	0.	0.	1.0
22	Si Na -	19.	0.	0.	77.	0.	2.	0.	0.	1.	0.	2.	0.	0.	0.	0.	1.9
64	Ca Si Al	3.	3.	17.	23.	0.	5.	0.	0.	41.	1.	6.	0.	0.	0.	0.	4.0
24	Si Ca Al	7.	0.	21.	34.	1.	3.	0.	0.	26.	2.	6.	0.	0.	0.	0.	2.4
39	Si Al Ca	6.	0.	32.	40.	0.	2.	0.	0.	16.	1.	2.	0.	0.	0.	0.	4.5
4	Ca Al Si	0.	2.	17.	13.	0.	4.	0.	0.	56.	0.	8.	0.	0.	0.	0.	0.5
5	Ca Si Na	16.	1.	14.	22.	0.	14.	0.	0.	29.	1.	4.	0.	0.	0.	0.	0.6
4	Si Ca Na	13.	0.	9.	48.	0.	2.	0.	0.	20.	4.	4.	0.	0.	0.	0.	0.7
2	S Si Ti	0.	0.	9.	25.	0.	44.	0.	0.	4.	18.	0.	0.	0.	0.	0.	0.5
12	Ca S Al	5.	6.	10.	5.	0.	21.	0.	0.	46.	1.	5.	0.	0.	0.	0.	0.7
26	S Na Ca	26.	1.	4.	8.	0.	34.	0.	0.	17.	1.	7.	0.	1.	0.	0.	2.6
21	Ca S Na	12.	3.	5.	4.	0.	32.	0.	0.	41.	1.	3.	0.	0.	0.	0.	2.3
31	S Ca Na	18.	1.	4.	5.	0.	38.	0.	0.	27.	1.	7.	0.	0.	0.	0.	3.2
100	Si Na Al	29.	0.	25.	36.	0.	3.	0.	0.	3.	1.	2.	0.	0.	0.	0.	9.7
156	Si Al Na	21.	0.	31.	39.	0.	2.	0.	0.	4.	1.	3.	0.	0.	0.	0.	11.7
4	Al Si Na	22.	0.	30.	28.	0.	8.	0.	0.	8.	0.	4.	0.	0.	0.	0.	0.7
33	Na Si Al	35.	0.	23.	30.	0.	4.	0.	1.	3.	1.	4.	0.	0.	0.	0.	3.5
14	Fe Ca Si	0.	0.	6.	12.	0.	5.	0.	0.	20.	1.	55.	0.	0.	0.	0.	1.0
13	Ca Fe Si	0.	4.	10.	14.	0.	5.	0.	0.	44.	2.	21.	0.	0.	0.	0.	0.8
10	Ca Si Fe	6.	2.	11.	19.	0.	8.	0.	0.	40.	0.	13.	0.	0.	0.	0.	0.7
7	Si Ca Fe	1.	0.	10.	37.	0.	5.	0.	0.	28.	2.	16.	0.	1.	0.	0.	0.5
13	Ca Mg S	0.	15.	3.	3.	0.	9.	0.	0.	64.	1.	3.	0.	0.	0.	0.	0.8
42	Ca S Mg	1.	11.	4.	4.	0.	20.	0.	0.	54.	1.	5.	0.	0.	0.	0.	2.5
16	Ca Si S	1.	2.	8.	20.	0.	13.	0.	1.	45.	2.	8.	0.	1.	0.	0.	1.3
35	Ca S Si	1.	5.	8.	12.	0.	19.	0.	0.	48.	1.	6.	0.	0.	0.	0.	2.2
16	S Ca Si	1.	0.	7.	16.	0.	34.	0.	1.	26.	2.	9.	0.	3.	0.	0.	0.8
11	S Fe Ca	11.	0.	8.	13.	0.	27.	0.	0.	18.	1.	21.	0.	1.	0.	0.	0.9
11	Fe Ca S	0.	2.	1.	5.	0.	15.	0.	0.	31.	1.	43.	0.	1.	0.	0.	1.8

TABLE 4-57. - PSIT/SECV Beulah ash probe (horiz. duct.) on filter (Cont.)

28	Ca S Fe	0.	4.	5.	5.	0.	28.	0.	0.	45.	0.	13.	0.	0.	0.	0.	2.5
14	S Ca Fe	0.	0.	8.	11.	0.	40.	0.	0.	26.	1.	14.	0.	1.	0.	0.	2.0
17	Ca Fe S	4.	3.	6.	6.	0.	15.	0.	0.	40.	1.	25.	0.	0.	0.	0.	1.9
4	Si Na S	19.	0.	1.	51.	0.	14.	0.	0.	8.	1.	5.	1.	0.	0.	0.	0.9
5	S Na Si	25.	0.	7.	15.	0.	34.	0.	0.	11.	2.	5.	0.	0.	0.	0.	0.7
4	Fe Si Na	17.	0.	13.	19.	0.	4.	0.	0.	6.	2.	39.	0.	0.	0.	0.	0.7
6	Ca Al Mg	0.	12.	16.	5.	0.	7.	0.	0.	56.	0.	5.	0.	0.	0.	0.	0.5
10	Fe Si Al	11.	0.	17.	22.	0.	4.	0.	0.	6.	0.	40.	0.	0.	0.	0.	1.1
11	Si Al Fe	4.	0.	32.	42.	0.	1.	0.	0.	6.	0.	15.	0.	0.	0.	0.	0.8
2	Ca Si Ti	0.	0.	7.	21.	0.	9.	0.	0.	42.	17.	3.	0.	0.	0.	0.	0.5
32	OTHERS -	13.	2.	15.	17.	0.	16.	0.	0.	12.	1.	22.	0.	0.	0.	0.	2.8
165	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.3
1199	TOTALS -	12.	2.	14.	23.	0.	12.	0.	0.	25.	1.	11.	0.	0.	0.	0.	100.0

SAMPLE # 597 PSI Beulah ash probe (horiz. duct.) on filter
NUMBER 597 DISK 53 FILE 117 - 120 PARTICLES
RUN 1 DATE 26-JUL-91 SUMMARY 120 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca S -	4.6	8.	35.	31.	26.	0.	0.	0.
Si Na Al	9.7	22.	59.	18.	1.	0.	0.	0.
Si Al Na	11.7	21.	39.	33.	7.	0.	0.	0.
Si Al Ca	4.5	13.	63.	15.	9.	0.	0.	0.
OTHERS -	69.4	13.	49.	32.	6.	0.	0.	0.
TOTALS -	100.0	15.	49.	30.	7.	0.	0.	0.

TABLE 4-58. - SECV/PSIT Beulah Lignite precipitator ash collected from electrostatic PR

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 601 SECV/PSI BEULAH LIGNITE PRECIP. ASH COLLECTED FROM ELECTROSTATIC PR
 NUMBER 601 DISK 40 FILE 121 - 124 PARTICLES
 RUN 1 DATE 25-DEC-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.21267E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
38	Ca - -	0.	2.	1.	1.	0.	3.	0.	0.	90.	0.	2.	0.	0.	0.	0.	2.3
44	Fe - -	3.	0.	2.	3.	0.	4.	0.	0.	2.	0.	86.	0.	0.	0.	0.	3.7
53	Ca S -	1.	0.	0.	0.	0.	26.	0.	0.	72.	0.	0.	0.	0.	0.	0.	2.5
24	Si Na -	26.	0.	0.	68.	0.	4.	0.	0.	0.	0.	2.	0.	0.	0.	0.	1.1
11	Na S -	49.	0.	0.	2.	0.	43.	0.	1.	3.	0.	0.	0.	0.	0.	0.	1.0
8	S Na -	40.	0.	3.	3.	0.	46.	0.	0.	4.	1.	2.	0.	0.	0.	0.	0.9
5	Fe S Ca	9.	1.	3.	3.	0.	15.	0.	0.	11.	2.	56.	0.	0.	0.	0.	0.7
14	Ca Fe S	6.	5.	7.	6.	0.	16.	0.	0.	38.	1.	20.	0.	0.	0.	0.	1.2
15	Fe Ca S	4.	0.	1.	1.	0.	9.	0.	0.	25.	0.	59.	0.	0.	0.	0.	1.3
19	Ca S Fe	6.	6.	4.	6.	0.	24.	0.	0.	41.	2.	11.	0.	0.	0.	0.	1.6
217	Si Al Na	22.	0.	29.	36.	0.	5.	0.	0.	4.	1.	3.	0.	0.	0.	0.	15.9
35	Na Si Al	35.	0.	22.	28.	0.	11.	0.	0.	3.	1.	1.	0.	0.	0.	0.	2.5
71	Si Na Al	28.	0.	25.	32.	0.	8.	0.	0.	2.	1.	3.	0.	0.	0.	0.	9.1
49	Ca Si Al	8.	1.	18.	24.	0.	5.	0.	0.	38.	0.	6.	0.	0.	0.	0.	3.5
32	Si Al Ca	11.	0.	26.	34.	0.	4.	0.	0.	18.	3.	5.	0.	0.	0.	0.	3.1
12	Si Ca Al	16.	0.	21.	29.	0.	5.	0.	0.	23.	1.	5.	0.	0.	0.	0.	0.5
39	Ca S Mg	5.	11.	3.	2.	0.	21.	0.	0.	53.	0.	3.	0.	0.	0.	0.	2.7
15	Ca Mg S	0.	14.	3.	1.	0.	10.	1.	0.	68.	0.	2.	0.	0.	0.	0.	0.6
19	Ca S Si	5.	3.	8.	12.	0.	18.	0.	0.	47.	0.	8.	0.	0.	0.	0.	2.6
7	Ca Si S	10.	4.	13.	19.	0.	15.	0.	0.	33.	0.	5.	0.	0.	0.	0.	0.9
24	Ca S Na	14.	5.	5.	4.	0.	31.	0.	0.	38.	0.	3.	0.	0.	0.	0.	4.1
38	S Ca Na	18.	3.	2.	3.	0.	43.	0.	0.	30.	0.	3.	0.	0.	0.	0.	4.6
63	S Na Ca	37.	2.	2.	2.	0.	42.	0.	0.	17.	1.	2.	0.	0.	0.	0.	8.3
17	Na S Ca	48.	1.	3.	3.	0.	36.	0.	1.	12.	0.	1.	0.	0.	0.	0.	1.4
20	Na S Si	36.	0.	12.	16.	0.	26.	0.	1.	5.	1.	4.	0.	0.	0.	0.	2.2
17	Si Na S	30.	0.	1.	51.	0.	14.	0.	0.	3.	1.	1.	0.	0.	0.	0.	1.1
10	S Na Si	28.	0.	6.	11.	0.	40.	0.	0.	4.	3.	1.	1.	0.	0.	0.	1.1
6	Na Si S	31.	0.	18.	23.	0.	18.	0.	0.	5.	1.	3.	0.	0.	0.	0.	0.8
4	Fe Ca Al	4.	5.	16.	14.	0.	3.	0.	0.	22.	0.	36.	0.	0.	0.	0.	0.6
12	Fe Na S	20.	0.	3.	2.	0.	17.	0.	0.	3.	2.	53.	0.	1.	0.	0.	0.7
9	Na S Fe	31.	0.	7.	10.	0.	28.	0.	0.	9.	1.	14.	0.	0.	0.	0.	1.0
13	Fe S Na	14.	0.	5.	5.	0.	17.	0.	0.	4.	0.	53.	0.	0.	0.	0.	1.1

TABLE 4-58. - SECV/PSIT Beulah Lignite precipitator ash collected from electrostatic PR (Cont.)

3	Ca Si Na	17.	0.	14.	21.	0.	14.	0.	0.	30.	0.	4.	0.	0.	0.	1.0
2	Ca S Ti	0.	0.	8.	10.	0.	24.	0.	0.	35.	17.	6.	0.	0.	0.	0.5
10	S Na Ti	31.	0.	3.	5.	0.	43.	0.	0.	6.	11.	1.	0.	0.	0.	1.0
6	S Ti Na	10.	0.	0.	3.	0.	51.	0.	0.	2.	34.	1.	0.	0.	0.	0.7
4	Ca Mg Si	0.	18.	9.	10.	0.	4.	0.	0.	53.	0.	7.	0.	0.	0.	0.9
49	OTHERS -	17.	1.	7.	8.	0.	27.	0.	2.	8.	3.	26.	0.	0.	0.	5.0
159	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE															5.3
1193	TOTALS -	18.	2.	12.	17.	0.	18.	0.	0.	20.	2.	10.	0.	0.	0.	100.0

SAMPLE # 601 SECV/PSI BEULAH LIGNITE PRECIP. ASH COLLECTED FROM ELECTROSTATIC PR
NUMBER 601 DISK 40 FILE 121 - 124 PARTICLES
RUN 1 DATE 25-DEC-91 SUMMARY 124 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Si Al Na	15.9	38.	35.	22.	4.	2.	0.	0.
Si Na Al	9.1	34.	58.	8.	0.	0.	0.	0.
Ca S Na	4.1	33.	59.	6.	3.	0.	0.	0.
S Ca Na	4.6	14.	64.	12.	10.	0.	0.	0.
S Na Ca	8.3	41.	53.	4.	2.	0.	0.	0.
OTHERS -	5.0	57.	38.	4.	1.	0.	0.	0.
OTHERS -	53.0	23.	43.	21.	11.	1.	0.	0.
TOTALS -	100.0	29.	46.	17.	7.	1.	0.	0.

TABLE 4-59. - Arizona ash Loy Yang 2301, 2.4 kg/h, 1275°C,
port 11, impactors #1 + cup

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 573 PSI/ARIZONA ASH LOY YANG 2301 2.4KG/HR 1275C PORT 11 IMP #1 + CUP.

NUMBER 573 DISK 40 FILE 133 - 136 PARTICLES

RUN 1 DATE 30-DEC-91 SUMMARY 136 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.14663E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
327	Ca - -	0.	1.	0.	0.	0.	4.	2.	0.	92.	0.	0.	0.	0.	0.	0.	22.1
185	Ca S -	0.	2.	0.	1.	0.	32.	1.	0.	64.	0.	0.	0.	0.	0.	0.	15.6
7	Ca Cl -	1.	1.	0.	0.	0.	3.	14.	0.	81.	0.	0.	0.	0.	0.	0.	0.6
5	Ca Cl Mg	1.	16.	3.	0.	0.	12.	19.	0.	48.	0.	2.	0.	0.	0.	0.	0.8
13	Ca Mg Cl	0.	20.	1.	1.	0.	7.	11.	0.	57.	0.	3.	0.	0.	0.	0.	0.6
239	Ca S Mg	0.	10.	0.	1.	0.	25.	4.	0.	56.	0.	2.	0.	0.	0.	0.	26.8
7	S Ca Mg	0.	16.	2.	2.	0.	37.	9.	3.	24.	3.	3.	0.	2.	0.	0.	0.5
17	Ca Mg S	0.	20.	5.	2.	0.	14.	8.	0.	47.	0.	4.	0.	0.	0.	0.	1.3
127	Ca S Cl	2.	5.	0.	1.	0.	23.	11.	1.	56.	0.	1.	0.	0.	0.	0.	12.0
35	Ca Cl S	5.	6.	1.	1.	0.	15.	21.	1.	50.	0.	1.	0.	0.	0.	0.	2.1
12	S Ca Cl	0.	4.	1.	1.	1.	43.	16.	3.	29.	0.	1.	0.	0.	0.	0.	1.7
8	Ca S Na	14.	4.	1.	1.	0.	25.	10.	2.	41.	0.	1.	1.	0.	0.	0.	1.3
11	Ca S Fe	0.	4.	0.	1.	0.	24.	4.	0.	57.	0.	10.	0.	0.	0.	0.	0.5
1	Fe Ca S	0.	0.	0.	0.	0.	9.	3.	0.	37.	0.	51.	0.	0.	0.	0.	0.5
15	Ca S Si	1.	6.	1.	11.	0.	24.	2.	1.	53.	0.	2.	0.	0.	0.	0.	1.7
7	Cl Na Ca	21.	1.	0.	1.	0.	6.	55.	0.	15.	0.	1.	0.	0.	0.	0.	0.6
2	Ca Si Mg	0.	13.	3.	23.	0.	11.	5.	0.	42.	1.	2.	0.	0.	0.	0.	0.5
158	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																10.8
1180	TOTALS -	1.	6.	1.	2.	0.	20.	6.	1.	61.	0.	2.	0.	0.	0.	0.	100.0

**TABLE 4-59. - Arizona ash Loy Yang 2301, 2.4 kg/h, 1275°C,
port 11, impactors #1 + cup (Cont.)**

SAMPLE # 573 PSI/ARIZONA ASH LOY YANG 2301 2.4KG/HR 1275C PORT 11 IMP #1 + CUP.
NUMBER 573 DISK 40 FILE 133 - 136 PARTICLES
RUN 1 DATE 30-DEC-91 SUMMARY 136 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	22.1	22.	40.	11.	19.	8.	1.	0.
Ca S -	15.6	8.	16.	13.	47.	15.	1.	0.
Ca S Mg	26.8	2.	10.	14.	63.	10.	1.	0.
Ca S Cl	12.0	1.	2.	8.	60.	29.	2.	0.
OTHERS -	23.5	6.	8.	16.	43.	20.	6.	0.
TOTALS -	100.0	8.	16.	13.	46.	15.	2.	0.

**TABLE 4-60. - Arizona Loy Yang 2301 ash on filter. 2.4 kg/h.
1275°C. port 11. impactors 2+3+4**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 574 PSI/ARIZONA LOY YANG 2301 ASH ON FILTER 2.4KG/HR, 1275C, PORT 11, IMP 2+3+4

NUMBER 574 DISK 52 FILE 113 - 116 PARTICLES

RUN 1 DATE 7-APR-92 SUMMARY 116 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.28009E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
222	Ca - -	0.	1.	0.	0.	0.	4.	1.	1.	92.	0.	0.	0.	0.	0.	0.	20.2
5	Na - -	96.	0.	0.	0.	0.	0.	2.	0.	2.	0.	0.	0.	0.	0.	0.	1.0
342	Ca S -	0.	1.	0.	0.	0.	37.	0.	0.	60.	0.	1.	0.	0.	0.	0.	30.6
8	S Ca -	1.	0.	0.	0.	0.	56.	0.	0.	44.	0.	0.	0.	0.	0.	0.	1.9
11	Ca Mg -	0.	11.	0.	0.	0.	1.	0.	0.	86.	0.	1.	0.	0.	0.	0.	2.2
13	Mg Ca -	0.	69.	0.	2.	0.	3.	0.	0.	21.	0.	4.	0.	0.	0.	0.	0.8
128	Ca S Mg	0.	12.	1.	2.	0.	29.	0.	0.	52.	0.	4.	0.	0.	0.	0.	11.0
21	Mg Ca S	0.	49.	2.	2.	0.	14.	0.	0.	26.	0.	4.	0.	2.	0.	0.	1.6
23	Ca Mg S	0.	25.	5.	2.	0.	16.	0.	0.	47.	0.	4.	0.	0.	0.	0.	1.7
16	Ca S Cl	1.	2.	0.	1.	0.	34.	10.	1.	50.	0.	1.	0.	0.	0.	0.	1.2
13	Ca Cl S	0.	6.	0.	0.	0.	16.	24.	1.	50.	0.	1.	1.	1.	0.	0.	0.5
5	S Cl Ca	0.	0.	0.	0.	0.	39.	35.	0.	22.	0.	0.	0.	3.	0.	0.	0.7
5	Cl K S	0.	0.	0.	5.	0.	17.	50.	24.	4.	0.	0.	0.	0.	0.	0.	0.8
58	Ca S Fe	0.	1.	2.	1.	0.	31.	0.	0.	53.	0.	11.	0.	0.	0.	0.	4.7
4	Ca Fe S	0.	7.	2.	2.	0.	11.	0.	0.	54.	0.	23.	0.	2.	0.	0.	1.0
31	Ca S Si	0.	2.	3.	10.	0.	27.	0.	1.	54.	0.	2.	0.	0.	0.	0.	3.2
17	Ca S Al	0.	2.	11.	4.	1.	24.	0.	0.	51.	1.	6.	0.	0.	0.	0.	1.8
4	Si Al Na	17.	0.	27.	37.	0.	5.	0.	3.	9.	0.	2.	0.	0.	0.	0.	0.6
8	Mg Ca Si	0.	45.	6.	10.	0.	1.	0.	0.	34.	0.	4.	0.	0.	0.	0.	0.6
10	Ca Si Al	2.	2.	14.	21.	0.	2.	0.	0.	52.	3.	3.	0.	0.	0.	0.	0.5
19	Mg Ca Fe	0.	57.	3.	2.	0.	5.	0.	0.	22.	0.	10.	0.	0.	0.	0.	0.9
7	Ca Mg Al	0.	26.	13.	5.	0.	6.	0.	1.	46.	0.	3.	0.	0.	0.	0.	0.7
6	Ca Al Mg	0.	17.	24.	7.	0.	2.	0.	0.	43.	0.	7.	0.	0.	0.	0.	0.6
4	Ca S P	0.	0.	0.	0.	8.	39.	0.	0.	53.	0.	0.	0.	0.	0.	0.	1.4
1	Cl S P	0.	0.	0.	0.	20.	23.	23.	0.	14.	18.	0.	0.	0.	0.	0.	0.5
11	OTHERS -	0.	14.	10.	3.	0.	2.	0.	0.	33.	0.	37.	0.	1.	0.	0.	0.7
144	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.7

**TABLE 4-60. - Arizona Loy Yang 2301 ash on filter, 2.4 kg/h,
1275°C, port 11, impactors 2+3+4 (Cont.)**

1136 TOTALS - 1. 6. 2. 2. 0. 23. 2. 1. 58. 0. 3. 0. 0. 0. 0. 100.0

SAMPLE 574 PSI/ARIZONA LOY YANG 2301 ASH ON FILTER 2.4KG/HR, 1275C, PORT 11, IMP
NUMBER 574 DISK 52 FILE 113 - 116 PARTICLES
RUN 1 DATE 7-APR-92 SUMMARY 116 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PY. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	20.2	13.	41.	17.	14.	11.	3.	0.
Ca S -	30.6	24.	21.	27.	20.	7.	1.	0.
Ca S Mg	11.0	28.	13.	27.	24.	5.	1.	0.
Ca S Fe	4.7	65.	8.	22.	3.	3.	0.	0.
OTHERS -	33.5	42.	20.	9.	14.	8.	7.	0.
TOTALS -	100.0	30.	23.	19.	17.	8.	3.	0.

**TABLE 4-61. - Arizona Loy Yang 2301, 2.4 kg/h, 1275°C,
port 11, impactors 5+6+7+8+AF**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 575 PSI/ARIZONA LOY YANG 2301 2.4KG/HR 1275C PORT 11 IMPS 5+6+7+8+AF
NUMBER 575 DISK 52 FILE 117 - 120 PARTICLES
RUN 1 DATE 10-APR-92 SUMMARY 120 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.29751E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
6	S - -	0.	1.	1.	0.	0.	92.	2.	0.	3.	1.	0.	0.	0.	0.	0.	0.5
309	Cl Na -	36.	0.	0.	0.	0.	3.	57.	0.	3.	0.	0.	0.	0.	0.	0.	27.4
3	S Cl -	0.	0.	0.	0.	0.	83.	15.	0.	1.	0.	0.	0.	0.	0.	0.	0.9
2	S Ca -	0.	0.	0.	0.	0.	72.	0.	0.	28.	0.	0.	0.	0.	0.	0.	0.5
1	S Mg -	0.	13.	0.	0.	0.	77.	0.	0.	5.	0.	0.	5.	0.	0.	0.	0.5
24	Cl S Ca	1.	5.	0.	1.	0.	25.	46.	3.	16.	0.	1.	1.	0.	0.	0.	1.8
10	Ca S Cl	0.	4.	0.	0.	0.	35.	16.	6.	39.	0.	0.	0.	0.	0.	0.	0.9
29	S Cl Ca	1.	4.	1.	1.	0.	46.	26.	1.	15.	1.	2.	1.	2.	0.	0.	3.1
16	S Ca Cl	3.	5.	0.	2.	0.	47.	15.	3.	21.	1.	2.	0.	2.	0.	0.	1.4
11	Cl Ca S	2.	5.	0.	1.	0.	19.	44.	4.	22.	0.	3.	0.	0.	0.	0.	1.5
308	Cl Na S	28.	2.	0.	0.	0.	11.	50.	1.	6.	0.	1.	0.	0.	0.	0.	25.8
11	S Cl Na	19.	4.	0.	1.	0.	37.	26.	2.	7.	0.	3.	0.	0.	0.	0.	0.8
35	Cl S Na	18.	3.	0.	0.	0.	26.	38.	3.	10.	0.	1.	0.	0.	0.	0.	2.6
6	Na Cl S	51.	3.	0.	0.	0.	12.	26.	0.	8.	0.	0.	0.	0.	0.	0.	0.6
9	S K Ca	2.	2.	0.	0.	0.	38.	4.	33.	22.	0.	0.	0.	0.	0.	0.	0.7
7	K S Ca	1.	5.	0.	0.	0.	32.	5.	34.	22.	0.	1.	0.	0.	0.	0.	0.8
2	S Ca Si	0.	0.	0.	8.	0.	63.	2.	7.	17.	0.	0.	0.	3.	0.	0.	0.5
10	Cl Na K	25.	0.	0.	0.	0.	12.	42.	13.	8.	0.	0.	0.	0.	0.	0.	0.6
118	Cl Na Ca	28.	2.	0.	0.	0.	7.	50.	1.	9.	0.	1.	0.	0.	0.	0.	10.2
15	Cl S K	10.	1.	0.	0.	0.	23.	33.	19.	13.	0.	1.	0.	0.	0.	0.	1.2
27	Ca S Mg	0.	18.	1.	1.	0.	29.	7.	1.	35.	1.	5.	0.	1.	0.	0.	1.4
13	S Mg Ca	0.	25.	0.	2.	0.	41.	4.	3.	12.	1.	4.	0.	0.	0.	0.	0.8
19	S Ca Mg	3.	18.	0.	1.	0.	37.	6.	2.	29.	1.	3.	0.	0.	0.	0.	1.3
12	Mg S Ca	0.	40.	0.	2.	0.	25.	5.	2.	22.	1.	8.	0.	0.	0.	0.	0.5
9	Mg Ca S	0.	34.	0.	0.	0.	19.	12.	3.	25.	1.	3.	0.	3.	0.	0.	0.5
19	Cl Na Mg	27.	11.	0.	0.	0.	7.	45.	1.	5.	0.	2.	0.	0.	0.	0.	1.6
7	Cl S Mg	5.	16.	0.	1.	4.	20.	38.	0.	10.	1.	4.	0.	1.	0.	0.	0.8
11	S Cl Mg	0.	15.	0.	1.	0.	45.	29.	1.	6.	0.	1.	0.	1.	0.	0.	1.9
6	S Mg Cl	0.	21.	0.	3.	2.	39.	18.	0.	15.	0.	1.	0.	0.	0.	0.	1.2
5	Mg Cl S	5.	36.	0.	2.	0.	19.	20.	0.	12.	0.	6.	0.	0.	0.	0.	0.6

**TABLE 4-62. - Arizona ash Loy Yang 2301, 3.8 kg/h, 1420°C,
port 11, impactors 1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 576 PSI/ARIZONA ASH LOY YANG 2301 3.8 KG/HR. 1420C PORT 11 IMP. 1 + CUP
NUMBER 576 DISK 40 FILE 101 - 104 PARTICLES
RUN 3 DATE 20-DEC-91 SUMMARY 104 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.20479E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
478	Ca - -	0.	2.	0.	0.	0.	5.	2.	0.	90.	0.	0.	0.	0.	0.	0.	44.7
268	Ca S -	0.	2.	0.	0.	0.	29.	1.	0.	67.	0.	1.	0.	0.	0.	0.	20.7
10	Ca Cl -	1.	1.	0.	0.	0.	2.	21.	0.	73.	0.	0.	0.	1.	0.	0.	1.1
177	Ca S Mg	0.	10.	1.	1.	0.	25.	5.	0.	54.	0.	3.	0.	0.	0.	0.	14.9
19	Ca Mg S	0.	20.	1.	3.	0.	13.	6.	0.	53.	0.	3.	0.	0.	0.	0.	1.2
17	Ca Cl S	3.	4.	0.	1.	0.	14.	23.	0.	53.	0.	1.	0.	0.	0.	0.	0.9
65	Ca S Cl	0.	6.	1.	1.	0.	25.	10.	0.	54.	0.	3.	0.	0.	0.	0.	5.1
17	Ca S Fe	0.	4.	0.	1.	0.	22.	4.	0.	59.	1.	9.	0.	0.	0.	0.	1.6
14	Ca Mg Cl	0.	20.	2.	3.	0.	8.	11.	1.	51.	1.	4.	0.	0.	0.	0.	1.3
7	Mg Cl Ca	0.	63.	0.	2.	0.	4.	20.	0.	10.	0.	1.	0.	0.	0.	0.	0.8
118	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																7.6
1192	TOTALS -	0.	5.	1.	2.	0.	15.	4.	0.	71.	0.	2.	0.	0.	0.	0.	100.0

SAMPLE # 576 PSI/ARIZONA ASH LOY YANG 2301 3.8 KG/HR. 1420C PORT 11 IMP. 1 + CUP
NUMBER 576 DISK 40 FILE 101 - 104 PARTICLES
RUN 3 DATE 20-DEC-91 SUMMARY 104 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca - -	44.7	38.	36.	13.	10.	3.	0.	0.
Ca S -	20.7	13.	28.	20.	26.	12.	0.	0.
Ca S Mg	14.9	20.	17.	20.	36.	7.	0.	0.
Ca S Cl	5.1	1.	35.	20.	32.	12.	0.	0.
OTHERS -	14.6	31.	16.	15.	26.	9.	3.	0.
TOTALS -	100.0	27.	29.	16.	21.	7.	0.	0.

**TABLE 4-63. - Arizona Loy Yang 2301 run 49h. 3.8 kg/h.
1420°C. port 11. impactors 2+3+4**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 577 PSI/UA LOY YANG 2301 RUN 49H 3.8 KG/HR 1420C PORT 11 IMP 2+3+4
NUMBER 577 DISK 58 FILE 105 - 108 PARTICLES
RUN 1 DATE 15-MAY-92 SUMMARY 108 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.54685E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
30	Ca - -	0.	3.	0.	0.	0.	6.	0.	0.	88.	0.	1.	0.	2.	0.	0.	1.0
6	S - -	0.	0.	0.	0.	0.	98.	0.	0.	0.	0.	0.	0.	0.	0.	0.	1.7
10	Mg - -	0.	84.	0.	4.	0.	3.	0.	0.	4.	0.	5.	0.	1.	0.	0.	0.7
108	Ca S -	0.	1.	0.	0.	0.	43.	0.	0.	56.	0.	0.	0.	0.	0.	0.	10.0
8	S Ca -	0.	0.	0.	1.	0.	54.	0.	0.	40.	4.	0.	0.	0.	0.	0.	0.9
27	Cl Na -	31.	0.	0.	0.	0.	1.	67.	0.	1.	0.	0.	0.	0.	0.	0.	0.9
5	Si Al -	0.	0.	47.	49.	0.	0.	0.	0.	0.	3.	0.	0.	0.	0.	0.	0.8
2	K Cl Ca	0.	0.	0.	12.	0.	11.	27.	35.	15.	0.	0.	0.	0.	0.	0.	0.8
1	K Ca Cl	0.	0.	0.	9.	0.	20.	22.	25.	24.	0.	0.	0.	0.	0.	0.	0.5
7	Ca S Cl	3.	2.	0.	0.	0.	32.	11.	0.	49.	0.	1.	0.	0.	0.	0.	0.7
3	Cl S Ca	0.	0.	0.	0.	0.	29.	33.	8.	24.	0.	6.	0.	0.	0.	0.	1.3
256	Ca Mg S	0.	24.	2.	2.	0.	17.	1.	0.	45.	0.	8.	0.	0.	0.	0.	14.0
173	Ca S Mg	0.	15.	1.	1.	0.	26.	1.	0.	48.	0.	7.	0.	1.	0.	0.	13.8
17	S Ca Mg	0.	17.	0.	1.	0.	44.	0.	3.	26.	0.	8.	0.	2.	0.	0.	1.2
131	Mg Ca S	0.	42.	3.	3.	0.	16.	2.	1.	24.	0.	9.	0.	0.	0.	0.	14.1
4	Mg S Ca	0.	34.	4.	4.	0.	25.	0.	0.	21.	0.	12.	0.	0.	0.	0.	0.6
3	Cl S K	0.	0.	0.	18.	0.	25.	33.	22.	1.	0.	0.	0.	1.	0.	0.	0.8
38	Ca S Fe	0.	2.	1.	0.	0.	32.	1.	1.	49.	0.	12.	1.	0.	0.	0.	5.1
7	S Ca Fe	0.	1.	0.	2.	0.	46.	0.	2.	36.	2.	10.	0.	0.	0.	0.	0.7
2	Ca S Cu	0.	0.	0.	0.	0.	31.	0.	0.	47.	0.	10.	12.	0.	0.	0.	0.7
57	Mg Ca Fe	0.	46.	1.	2.	0.	7.	2.	1.	24.	1.	14.	0.	1.	0.	0.	7.1
32	Ca Mg Fe	0.	27.	4.	2.	0.	8.	0.	3.	41.	0.	14.	0.	1.	0.	0.	2.3
10	Mg Fe Ca	0.	48.	1.	4.	1.	6.	1.	0.	16.	3.	18.	0.	1.	0.	0.	1.3
4	Mg Ca Cl	0.	52.	0.	3.	0.	7.	9.	0.	23.	0.	7.	0.	0.	0.	0.	1.0
3	Mg Fe S	0.	39.	9.	8.	0.	14.	0.	0.	10.	0.	20.	0.	0.	0.	0.	1.3
4	Ca Mg Al	0.	25.	11.	1.	0.	6.	5.	0.	43.	3.	6.	0.	0.	0.	0.	0.6
6	Ca S Al	0.	3.	11.	0.	0.	32.	0.	0.	46.	2.	4.	0.	2.	0.	0.	0.9
6	Ca S Zn	0.	0.	0.	0.	0.	38.	0.	0.	53.	0.	0.	0.	8.	0.	0.	0.5
7	Mg Ca Si	0.	41.	6.	11.	0.	4.	2.	0.	26.	3.	6.	0.	1.	0.	0.	1.0

TABLE 4-63. - Arizona Loy Yang 2301 run 49h, 3.8 kg/h.
1420°C, port 11, impactors 2+3+4 (Cont.)

5	Ca Mg Si	0.	16.	9.	12.	0.	6.	0.	0.	55.	0.	2.	0.	1.	0.	0.	0.8
1	Si Ca Mg	0.	11.	0.	39.	0.	9.	0.	0.	35.	0.	6.	0.	0.	0.	0.	0.6
1	Cl Ti Ca	0.	0.	0.	0.	0.	0.	55.	0.	17.	28.	0.	0.	0.	0.	0.	1.5
5	OTHERS -	0.	3.	3.	0.	0.	2.	0.	0.	2.	0.	1.	59.	30.	0.	0.	1.9
144	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.6
1123	TOTALS -	1.	20.	3.	4.	0.	22.	4.	1.	35.	1.	8.	1.	1.	0.	0.	100.0

SAMPLE 577 PSI/UA LOY YANG 2301 RUN 49H 3.8 KG/HR 1420C PORT 11 IMP 2+3+4
NUMBER 577 DISK 58 FILE 105 - 108 PARTICLES
RUN 1 DATE 15-MAY-92 SUMMARY 108 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca S -	10.0	13.	12.	8.	33.	23.	11.	0.
Ca Mg S	14.0	32.	20.	31.	11.	6.	0.	0.
Ca S Mg	13.8	46.	20.	15.	18.	2.	0.	0.
Mg Ca S	14.1	55.	32.	10.	2.	1.	0.	0.
Ca S Fe	5.1	64.	26.	1.	5.	5.	0.	0.
Mg Ca Fe	7.1	65.	30.	5.	1.	0.	0.	0.
OTHERS -	35.9	41.	25.	11.	7.	4.	8.	3.
TOTALS -	100.0	43.	24.	13.	11.	5.	4.	1.

**TABLE 4-64. - Arizona Loy Yang 2301 ash, 3.8 kg/h, 1420°C,
port 11, impactors 5+6+7+8**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 578 PSI/ARIZONA LOY YANG 2301 ASH 3.8 KG/HR 1420C PORT 11 IMP #5+6+7+8+
NUMBER 578 DISK 42 FILE 125 - 128 PARTICLES
RUN 1 DATE 14-JAN-92 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.29093E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
18	S - -	0.	6.	1.	2.	0.	80.	2.	1.	2.	1.	3.	0.	2.	0.	0.	2.5
4	Ca S -	0.	0.	0.	0.	0.	48.	0.	0.	52.	0.	0.	0.	0.	0.	0.	0.6
29	Cl Na -	31.	1.	0.	0.	0.	3.	63.	0.	3.	0.	0.	0.	0.	0.	0.	0.9
30	S Mg -	0.	18.	0.	0.	0.	76.	0.	1.	3.	1.	1.	0.	0.	0.	0.	3.5
63	S Cl Mg	0.	17.	1.	2.	0.	42.	22.	1.	9.	1.	4.	0.	0.	0.	0.	6.6
47	Cl Mg S	2.	25.	0.	1.	0.	18.	31.	1.	13.	1.	8.	0.	0.	0.	0.	4.3
83	S Mg Cl	0.	20.	1.	1.	0.	51.	14.	1.	8.	0.	4.	0.	0.	0.	0.	9.1
52	Cl S Mg	3.	19.	0.	1.	0.	22.	32.	2.	14.	0.	6.	0.	1.	0.	0.	3.9
33	Mg Cl S	0.	33.	1.	2.	0.	18.	23.	2.	13.	0.	8.	0.	0.	0.	0.	4.9
43	Mg S Cl	0.	32.	0.	1.	0.	23.	17.	2.	13.	1.	10.	0.	0.	0.	0.	2.5
49	S Ca Mg	0.	15.	0.	1.	0.	47.	7.	2.	21.	0.	6.	0.	1.	0.	0.	6.2
187	S Mg Ca	0.	21.	1.	1.	0.	52.	4.	1.	12.	0.	5.	0.	1.	0.	0.	17.0
82	Mg S Ca	0.	32.	1.	1.	0.	24.	12.	2.	18.	1.	8.	0.	0.	0.	0.	5.2
15	Ca S Mg	0.	21.	1.	1.	0.	26.	12.	1.	30.	0.	7.	0.	0.	0.	0.	1.0
28	Mg Ca S	0.	31.	1.	2.	0.	21.	13.	1.	23.	0.	7.	0.	0.	0.	0.	2.3
68	Cl Na S	22.	8.	0.	0.	0.	13.	44.	1.	7.	0.	3.	0.	0.	0.	0.	3.7
26	Cl S Na	17.	10.	0.	0.	0.	21.	37.	1.	10.	0.	4.	0.	0.	0.	0.	0.9
6	S Cl Na	18.	14.	0.	1.	0.	33.	22.	1.	8.	0.	0.	2.	0.	0.	0.	1.0
15	Cl Na Ca	22.	9.	0.	1.	0.	9.	43.	1.	11.	0.	4.	0.	0.	0.	0.	1.0
24	S Cl Ca	1.	13.	0.	1.	0.	39.	22.	3.	14.	1.	5.	0.	1.	0.	0.	1.5
21	Cl S Ca	2.	14.	0.	1.	0.	22.	36.	2.	17.	0.	6.	0.	0.	0.	0.	1.0
12	S Ca Cl	0.	8.	0.	1.	0.	53.	12.	2.	17.	0.	5.	0.	0.	0.	0.	0.8
21	Cl Mg Ca	1.	23.	0.	2.	0.	13.	36.	1.	17.	0.	6.	0.	0.	0.	0.	1.4
18	Mg Cl Ca	0.	31.	1.	3.	0.	14.	23.	1.	18.	0.	9.	0.	0.	0.	0.	1.5
6	Mg Ca Cl	0.	31.	1.	1.	0.	16.	17.	1.	20.	0.	13.	0.	0.	0.	0.	0.7
5	Cl Ca Mg	7.	16.	0.	0.	0.	13.	39.	0.	16.	0.	8.	0.	0.	0.	0.	0.7
5	S Mg K	0.	12.	0.	5.	0.	74.	0.	1.	1.	0.	0.	0.	0.	0.	0.	0.7
13	Cl Mg Na	16.	19.	0.	2.	0.	13.	33.	0.	11.	0.	5.	0.	0.	0.	0.	1.7
26	Cl Na Mg	24.	13.	0.	1.	0.	9.	39.	2.	9.	0.	4.	0.	0.	0.	0.	2.3
35	S Mg Fe	0.	20.	0.	1.	0.	59.	4.	1.	4.	0.	9.	0.	1.	0.	0.	1.7
21	Mg S Fe	0.	38.	0.	3.	1.	24.	9.	1.	10.	0.	13.	0.	1.	0.	0.	0.7
4	S Ca Fe	0.	1.	0.	1.	0.	66.	4.	2.	13.	0.	8.	2.	2.	0.	0.	0.5

**TABLE 4-64. - Arizona Loy Yang 2301 ash, 3.8 kg/h, 1420°C,
port 11, impactors 5+6+7+8 (Cont.)**

2	S	Fe	Ca	0.	0.	0.	0.	0.	78.	0.	0.	11.	0.	11.	0.	0.	0.	0.	0.8
1	S	Si	Mg	0.	11.	0.	11.	0.	73.	0.	0.	0.	0.	4.	0.	0.	0.	0.	0.5
4	S	Mg	Zn	0.	17.	0.	1.	0.	65.	0.	0.	4.	0.	4.	3.	6.	0.	0.	0.7
3	S	Mg	Al	0.	13.	6.	4.	0.	73.	0.	0.	1.	2.	1.	0.	0.	0.	0.	0.7
1	S	Fe	K	0.	0.	9.	0.	0.	63.	0.	9.	6.	0.	12.	0.	0.	0.	0.	0.6
78	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																		4.3
1181	TOTALS -			3.	19.	1.	2.	0.	38.	17.	2.	12.	0.	6.	0.	1.	0.	0.	100.0

SAMPLE # 578 PSI/ARIZONA LOY YANG 2301 ASH 3.8 KG/HR 1420C PORT 11 IMP #5+6+7+8+
NUMBER 578 DISK 42 FILE 125 - 128 PARTICLES
RUN 1 DATE 14-JAN-92 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S Cl Mg	6.6	14.	68.	16.	2.	0.	0.	0.
Cl Mg S	4.3	25.	52.	17.	6.	0.	0.	0.
S Mg Cl	9.1	18.	66.	15.	1.	0.	0.	0.
Mg Cl S	4.9	18.	75.	7.	0.	0.	0.	0.
S Ca Mg	6.2	25.	63.	12.	0.	0.	0.	0.
S Mg Ca	17.0	13.	67.	19.	1.	0.	0.	0.
Mg S Ca	5.2	49.	23.	25.	3.	0.	0.	0.
OTHERS -	46.8	26.	43.	23.	8.	1.	0.	0.
TOTALS -	100.0	23.	53.	19.	5.	0.	0.	0.

**TABLE 4-65. - Arizona Loy Yang 1953, 2.4 kg/h, 1160°C,
port 11, impactors #1 + cup**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 579 PSI/ARIZONA LOY YANG 1953, 2.4KG/HR, 1160C, PORT 11, IMP #1 + CUP.

NUMBER 579 DISK 42 FILE 121 - 124 PARTICLES

RUN 1 DATE 7-JAN-92 SUMMARY 124 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.11205E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
13	Si - -	1.	0.	2.	94.	0.	1.	0.	0.	0.	0.	1.	0.	0.	0.	0.	1.2
222	S - -	0.	0.	2.	1.	0.	90.	0.	1.	2.	1.	1.	0.	1.	0.	0.	19.2
9	Ca - -	0.	0.	0.	0.	0.	1.	1.	0.	98.	0.	0.	0.	0.	0.	0.	0.9
14	Fe - -	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	96.	0.	0.	0.	0.	1.3
61	S Ca -	0.	0.	1.	0.	0.	62.	0.	0.	35.	0.	1.	0.	0.	0.	0.	5.6
277	Ca S -	0.	0.	0.	0.	0.	46.	0.	0.	53.	0.	0.	0.	0.	0.	0.	22.6
11	Al S -	0.	0.	60.	0.	0.	35.	2.	1.	0.	0.	1.	0.	0.	0.	0.	0.9
7	S Al -	0.	1.	22.	3.	0.	70.	2.	0.	1.	0.	0.	0.	0.	0.	0.	0.6
14	S Mg -	0.	28.	0.	0.	0.	70.	0.	1.	1.	0.	0.	0.	0.	0.	0.	1.1
17	S Na -	21.	0.	0.	0.	0.	77.	0.	1.	1.	0.	0.	0.	0.	0.	0.	1.5
7	S K -	0.	0.	0.	0.	0.	84.	0.	16.	0.	0.	0.	0.	0.	0.	0.	0.8
9	Ca S Fe	0.	1.	3.	1.	0.	38.	0.	0.	47.	0.	9.	0.	0.	0.	0.	1.2
7	S Al Ca	0.	0.	21.	4.	0.	49.	1.	5.	14.	3.	1.	0.	2.	0.	0.	0.6
7	Ca S Al	0.	0.	9.	3.	0.	39.	0.	2.	45.	0.	2.	0.	0.	0.	0.	0.7
29	S Ca Al	0.	0.	14.	1.	0.	48.	0.	2.	32.	0.	1.	0.	1.	0.	0.	4.4
8	Al S Ca	3.	0.	43.	0.	1.	30.	3.	4.	14.	0.	2.	0.	0.	0.	0.	0.6
2	Ca Al S	0.	0.	29.	0.	0.	20.	8.	3.	36.	0.	4.	0.	0.	0.	0.	0.8
3	S Cl Mg	0.	24.	2.	2.	0.	38.	30.	0.	0.	1.	0.	0.	2.	0.	0.	0.5
7	S Mg K	0.	20.	3.	4.	0.	49.	5.	11.	4.	0.	3.	0.	0.	0.	0.	0.5
16	Al S Cl	1.	0.	58.	2.	0.	24.	9.	3.	1.	0.	1.	0.	0.	0.	0.	1.7
7	Ca Si Al	0.	1.	19.	25.	0.	8.	0.	3.	37.	1.	7.	0.	0.	0.	0.	1.2
8	S Ca K	0.	0.	1.	1.	0.	56.	0.	11.	28.	1.	0.	0.	2.	0.	0.	0.7
2	Ca Si S	1.	0.	9.	24.	0.	12.	5.	7.	38.	0.	3.	0.	0.	0.	0.	0.5
25	Si Al S	0.	0.	33.	40.	0.	21.	0.	2.	1.	0.	1.	0.	0.	0.	0.	2.6
13	S Si Al	0.	2.	20.	23.	0.	49.	0.	2.	2.	0.	2.	2.	0.	0.	0.	1.1
7	S Na Ca	17.	2.	1.	0.	0.	61.	0.	4.	10.	0.	4.	0.	0.	0.	0.	1.4
8	S Na Mg	27.	14.	0.	1.	0.	56.	0.	0.	0.	0.	1.	1.	0.	0.	0.	0.5
6	Si Al Na	14.	0.	26.	41.	0.	4.	0.	1.	8.	2.	3.	0.	0.	0.	0.	0.6

TABLE 4-65. - Arizona Loy Yang 1953, 2.4 kg/h, 1160°C,
port 11, impactors #1 + cup (Cont.)

5 S Al Fe	1.	1.	22.	13.	0.	35.	1.	1.	9.	0.	18.	0.	0.	0.	0.	0.9
9 Al S K	0.	1.	52.	0.	0.	30.	2.	11.	0.	0.	4.	0.	0.	0.	0.	1.4
6 S Al K	0.	0.	31.	0.	0.	44.	7.	14.	3.	1.	0.	0.	0.	0.	0.	0.5
113 OTHERS -	3.	5.	15.	12.	0.	34.	4.	4.	9.	2.	8.	1.	2.	0.	0.	11.5
159 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.7
1108 TOTALS -	2.	2.	9.	7.	0.	51.	2.	2.	21.	1.	4.	0.	1.	0.	0.	100.0

SAMPLE # 579 PSI/ARIZONA LOY YANG 1953, 2.4KG/HR, 1160C, PORT 11, IMP #1 + CUP.

NUMBER 579 DISK 42 FILE 121 - 124 PARTICLES

RUN 1 DATE 7-JAN-92 SUMMARY 124 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
S - -	19.2	53.	25.	12.	8.	1.	1.	0.
S Ca -	5.6	24.	31.	23.	21.	1.	0.	0.
Ca S -	22.6	16.	32.	34.	15.	1.	1.	0.
S Ca Al	4.4	16.	51.	13.	18.	2.	0.	0.
OTHERS -	11.5	26.	41.	16.	17.	0.	0.	0.
OTHERS -	36.6	14.	28.	23.	26.	6.	2.	0.
TOTALS -	100.0	24.	31.	22.	18.	3.	1.	0.

**TABLE 4-66. - Arizona Loy Yang 1953, 2.4 kg/h, 1160°C,
port 11, impactors 2+3+4**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE 580 PSI/ARIZONA LOY YANG 1953, 2.4KG/HR, 1160C, PORT 11, IMPS 2+3+4
NUMBER 580 DISK 49 FILE 122 - 125 PARTICLES
RUN 1 DATE 30-MAR-92 SUMMARY 125 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.12288E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
25	Mg - -	0.88.	0.	0.	1.	5.	0.	1.	2.	1.	0.	1.	1.	0.	0.		1.5
113	S - -	0.	0.	1.	1.	0.	91.	0.	0.	3.	1.	2.	0.	0.	0.	0.	11.6
8	Fe - -	0.	0.	1.	0.	0.	1.	0.	0.	2.	1.	90.	0.	4.	0.	0.	0.5
41	S Mg -	0.35.	0.	0.	0.	63.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	4.1
10	Mg S -	0.60.	0.	0.	0.	36.	0.	1.	2.	0.	1.	0.	0.	0.	0.	0.	0.7
138	S Ca -	0.	0.	1.	1.	0.	59.	0.	0.	37.	0.	1.	0.	0.	0.	0.	14.1
203	Ca S -	0.	0.	0.	0.	0.	46.	0.	0.	52.	0.	1.	0.	0.	0.	0.	19.6
8	S Na -	24.	0.	0.	2.	0.	69.	0.	0.	2.	0.	1.	0.	0.	0.	0.	1.0
18	S Fe Ca	2.	2.	5.	5.	0.	48.	0.	2.	15.	0.	19.	0.	0.	0.	0.	1.5
44	S Ca Fe	1.	2.	5.	3.	0.	47.	0.	2.	29.	0.	11.	0.	0.	0.	0.	3.5
27	Ca S Fe	0.	1.	4.	3.	0.	38.	0.	0.	43.	0.	10.	0.	0.	0.	0.	2.6
11	S Ca Na	13.	2.	0.	1.	0.	51.	1.	1.	26.	0.	3.	0.	0.	0.	0.	0.6
19	S Na Ca	34.	1.	1.	1.	0.	51.	0.	1.	10.	0.	1.	0.	0.	0.	0.	1.7
15	S Ca Si	0.	0.	3.	11.	0.	59.	0.	1.	24.	0.	2.	0.	0.	0.	0.	0.7
14	Ca S Si	0.	3.	3.	11.	0.	36.	0.	0.	41.	1.	5.	0.	0.	0.	0.	0.9
7	S Mg Ca	0.34.	1.	1.	0.	51.	0.	3.	8.	0.	2.	0.	0.	0.	0.	0.	0.7
20	S Ca Mg	1.16.	1.	1.	0.	47.	0.	0.	31.	0.	2.	0.	0.	0.	0.	0.	1.1
8	Mg S Ca	0.47.	1.	2.	0.	24.	1.	2.	17.	0.	6.	0.	0.	0.	0.	0.	0.6
9	Fe S Al	0.	6.	20.	6.	0.	21.	1.	4.	6.	2.	33.	1.	0.	0.	0.	1.0
7	S Fe Al	0.	9.	15.	5.	0.	41.	1.	5.	3.	0.	21.	0.	0.	0.	0.	1.4
11	S Fe Mg	0.12.	5.	4.	0.	50.	0.	1.	4.	4.	19.	0.	1.	0.	0.		1.6
44	S Na Mg	27.14.	1.	1.	0.	52.	0.	1.	2.	0.	2.	0.	0.	0.	0.	0.	5.2
5	S Ca Al	0.	1.	8.	3.	0.	41.	0.	3.	33.	3.	6.	2.	0.	0.	0.	0.9
8	Ca S Al	0.	1.	9.	1.	0.	40.	0.	0.	44.	0.	4.	0.	1.	0.	0.	0.6
7	Fe Mg Al	0.19.	16.	6.	0.	8.	0.	0.	1.	0.	49.	0.	1.	0.	0.		0.9
3	Ca S Zn	0.	0.	0.	0.	0.	42.	0.	0.	47.	0.	0.	0.	10.	0.	0.	1.1
132	OTHERS -	5.	8.	11.	12.	1.	25.	3.	2.	12.	6.	13.	1.	1.	0.	0.	10.8
160	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.1
1116	TOTALS -	3.	7.	3.	4.	0.	49.	1.	1.	23.	1.	6.	0.	1.	0.	0.	99.9

TABLE 4-66. - Arizona Loy Yang 1953, 2.4 kg/h, 1160°C.
port 11, impactors 2+3+4 (Cont.)

SAMPLE 580 PSI/ARIZONA LOY YANG 1953, 2.4KG/HR, 1160C, PORT 11, IMPS 2+3+4
 NUMBER - 580 DISK 49 FILE 122 - 125 PARTICLES
 RUN 1 DATE 30-MAR-92 SUMMARY 125 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S - -	11.6	38.	38.	14.	9.	1.	1.	0.
S Mg -	4.1	3.	7.	5.	49.	32.	3.	0.
S Ca -	14.1	17.	53.	22.	8.	0.	0.	0.
Ca S -	19.6	14.	49.	27.	10.	0.	0.	0.
S Na Mg	5.2	19.	53.	18.	7.	0.	3.	0.
OTHERS -	10.8	60.	21.	11.	8.	0.	0.	0.
OTHERS -	34.5	21.	29.	25.	15.	7.	3.	0.
TOTALS -	99.9	24.	37.	21.	13.	4.	1.	0.

**TABLE 4-67. - PSIT/Arizona Loy Yang 1953 ash. 2.4 kg/h. 1160°C.
port 11. impactors 5+6+7+8+A**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 581 PSI/ARIZONA LOY YANG 1953 ASH 2.4KG/HR 1160C PORT 11 IMP #5+6+7+8+A
NUMBER 581 DISK 42 FILE 129 - 132 PARTICLES
RUN 1 DATE 15-JAN-92 SUMMARY 132 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.18787E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
12	Cl - -	5.	0.	0.	0.	0.	1.	93.	0.	1.	0.	0.	0.	0.	0.	0.	0.8
48	S - -	2.	1.	1.	2.	0.	75.	0.	7.	4.	1.	5.	0.	1.	0.	0.	4.3
66	S Na -	35.	0.	0.	0.	0.	62.	0.	1.	0.	1.	1.	0.	0.	0.	0.	4.5
233	Cl Na -	25.	0.	0.	0.	0.	0.	75.	0.	0.	0.	0.	0.	0.	0.	0.	12.7
12	K S -	2.	1.	0.	0.	0.	40.	1.	55.	1.	0.	0.	0.	0.	0.	0.	0.5
19	S K -	0.	0.	0.	0.	0.	80.	0.	19.	0.	0.	0.	0.	1.	0.	0.	2.0
10	S Fe -	0.	0.	0.	0.	0.	85.	0.	0.	0.	0.	13.	0.	0.	0.	0.	0.7
29	S K Na	12.	2.	1.	1.	0.	49.	0.	24.	7.	0.	4.	0.	0.	0.	0.	2.3
99	S Na K	25.	2.	1.	1.	0.	52.	1.	10.	3.	1.	4.	0.	0.	0.	0.	10.9
37	Cl Na S	25.	1.	0.	1.	0.	15.	54.	3.	1.	0.	1.	0.	0.	0.	0.	2.2
9	S Na Cl	29.	0.	0.	0.	0.	56.	13.	2.	0.	0.	1.	0.	0.	0.	0.	0.9
4	Na S Cl	29.	3.	1.	4.	0.	27.	22.	3.	2.	0.	6.	0.	2.	0.	0.	0.5
14	Cl S Na	22.	0.	0.	0.	0.	28.	41.	5.	0.	0.	3.	0.	0.	0.	0.	2.3
7	S Cl Na	22.	2.	0.	2.	0.	38.	26.	4.	2.	0.	2.	0.	2.	0.	0.	1.0
9	S Na Mg	23.	14.	0.	2.	0.	52.	0.	5.	0.	0.	1.	0.	2.	0.	0.	2.5
59	S K Fe	0.	1.	1.	3.	0.	65.	0.	14.	4.	1.	10.	0.	1.	0.	0.	6.2
34	S Fe K	3.	2.	3.	3.	0.	61.	0.	11.	2.	1.	13.	0.	1.	0.	0.	4.0
15	S Ca K	0.	0.	0.	5.	0.	61.	0.	13.	13.	1.	7.	0.	1.	0.	0.	2.6
115	S K Ca	2.	1.	1.	1.	0.	55.	0.	24.	12.	0.	4.	0.	0.	0.	0.	9.3
5	S Mg K	0.	16.	0.	3.	0.	66.	0.	10.	2.	0.	2.	0.	0.	0.	0.	0.5
24	S Na Ca	26.	0.	0.	2.	0.	51.	0.	5.	10.	1.	4.	0.	1.	0.	0.	2.1
52	S Na Fe	22.	3.	1.	2.	0.	56.	0.	6.	2.	1.	8.	0.	1.	0.	0.	5.9
6	S Fe Na	10.	1.	2.	5.	0.	60.	0.	6.	2.	0.	11.	0.	4.	0.	0.	1.1
5	S Fe Mg	0.	12.	2.	1.	0.	53.	0.	7.	2.	0.	22.	1.	0.	0.	0.	0.6
8	S Mg Fe	5.	21.	4.	4.	0.	39.	5.	8.	0.	2.	11.	0.	3.	0.	0.	1.1
7	S K Si	0.	0.	3.	10.	0.	69.	0.	16.	2.	0.	0.	0.	0.	0.	0.	0.7
5	S K Zn	0.	0.	0.	1.	0.	64.	0.	18.	3.	1.	5.	0.	9.	0.	0.	0.5
4	Cl S Zn	0.	0.	0.	0.	0.	28.	41.	8.	1.	0.	4.	0.	17.	0.	0.	0.7

TABLE 4-67. - PSIT/Arizona Loy Yang 1953 ash, 2.4 kg/h, 1160°C.
port 11, impactors 5+6+7+8+A (Cont.)

9 S Fe Ca	0.	4.	2.	3.	0.	58.	0.	7.	11.	1.	12.	0.	2.	0.	0.	1.0
4 S Ca Fe	0.	0.	0.	0.	0.	76.	0.	2.	13.	0.	10.	0.	0.	0.	0.	1.3
6 S K Al	0.	0.	9.	3.	0.	65.	0.	16.	3.	0.	5.	0.	0.	0.	0.	1.2
7 S K Ti	0.	0.	0.	0.	0.	70.	0.	15.	0.	9.	3.	0.	3.	0.	0.	0.7
53 OTHERS -	7.	5.	3.	5.	0.	55.	2.	3.	1.	2.	11.	1.	4.	0.	0.	5.7
136 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.4
1162 TOTALS -	13.	2.	1.	2.	0.	47.	14.	9.	4.	1.	5.	0.	1.	0.	0.	100.0

SAMPLE # 581 PSI/ARIZONA LOY YANG 1953 ASH 2.4KG/HR 1160C PORT 11 IMP #5+6+7+8+A
NUMBER 581 DISK 42 FILE 129 - 132 PARTICLES
RUN 1 DATE 15-JAN-92 SUMMARY 132 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
S - -	4.3	62.	15.	10.	10.	4.	0.	0.
S Na -	4.5	27.	0.	6.	4.	28.	35.	0.
Cl Na -	12.7	1.	0.	7.	23.	43.	26.	0.
S K Fe	6.2	45.	37.	12.	5.	0.	0.	0.
S Fe K	4.0	44.	45.	10.	2.	0.	0.	0.
S Na K	10.9	56.	33.	9.	2.	0.	1.	0.
S K Ca	9.3	35.	41.	20.	3.	0.	0.	0.
S Na Fe	5.9	42.	40.	10.	8.	0.	0.	0.
OTHERS -	5.7	85.	14.	1.	0.	0.	0.	0.
OTHERS -	36.4	34.	30.	11.	11.	8.	7.	0.
TOTALS -	100.0	38.	26.	10.	9.	10.	7.	0.

TABLE 4-68. - PSIT/SECV Loy Yang test 1 ash probe (ring 7) on filter untreated

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 593 PSI Loy Yang test 1 ash probe (ring 7) on filter untreated

NUMBER 593 DISK 53 FILE 101 - 104 PARTICLES

RUN 1 DATE 15-JUL-91 SUMMARY 104 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.25881E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Si - -	3.	0.	1.	92.	0.	0.	0.	0.	1.	0.	2.	0.	1.	0.	0.	2.0
21	Fe - -	0.	2.	2.	0.	0.	0.	0.	0.	3.	1.	88.	0.	3.	0.	0.	2.2
9	Si Na -	17.	0.	0.	80.	0.	0.	0.	0.	1.	0.	1.	0.	2.	0.	0.	0.5
35	Si Na Al	21.	2.	13.	53.	0.	1.	0.	0.	3.	1.	5.	0.	2.	0.	0.	1.7
16	Si Al Na	15.	3.	25.	47.	0.	0.	0.	0.	3.	1.	5.	0.	2.	0.	0.	1.4
9	Si Al Fe	1.	0.	17.	74.	0.	0.	0.	0.	0.	0.	8.	0.	0.	0.	0.	0.5
19	Al Mg S	1.	21.	52.	1.	0.	11.	1.	1.	5.	0.	4.	0.	2.	0.	0.	1.2
187	Al Mg Ca	0.	27.	43.	3.	0.	3.	0.	0.	14.	1.	6.	0.	2.	0.	0.	17.5
29	Al Ca Mg	0.	16.	45.	4.	0.	1.	0.	1.	20.	1.	7.	0.	2.	0.	0.	2.8
72	Mg Ca Al	0.	52.	15.	3.	0.	1.	0.	0.	21.	0.	7.	0.	1.	0.	0.	8.0
162	Mg Al Ca	0.	42.	27.	4.	0.	3.	0.	0.	15.	1.	6.	0.	2.	0.	0.	15.3
14	Si Mg Ca	1.	24.	13.	35.	0.	0.	0.	0.	16.	2.	8.	0.	2.	0.	0.	0.7
15	Mg Si Ca	0.	45.	9.	24.	0.	0.	0.	0.	16.	1.	5.	0.	0.	0.	0.	0.8
12	Mg Ca Si	1.	43.	10.	16.	0.	1.	0.	0.	23.	0.	6.	0.	0.	0.	0.	0.9
18	Si Al Mg	1.	17.	21.	37.	0.	2.	0.	0.	10.	1.	8.	0.	2.	0.	0.	1.8
15	Al Si Mg	0.	16.	33.	26.	0.	0.	0.	1.	13.	0.	8.	0.	2.	0.	0.	1.4
20	Si Mg Al	1.	23.	18.	34.	0.	0.	0.	0.	10.	1.	9.	0.	4.	0.	0.	2.3
9	Mg Al Si	1.	38.	25.	16.	0.	3.	0.	0.	11.	1.	5.	0.	0.	0.	0.	0.5
14	Mg Si Al	1.	33.	18.	22.	0.	2.	0.	0.	12.	0.	11.	1.	1.	0.	0.	0.6
28	Al Mg Si	0.	25.	37.	16.	0.	1.	0.	0.	10.	2.	7.	0.	2.	0.	0.	2.6
30	Mg Ca Fe	0.	50.	7.	5.	0.	1.	0.	0.	24.	0.	13.	0.	0.	0.	0.	2.5
13	Si Al Ca	0.	4.	29.	41.	0.	1.	0.	2.	17.	1.	3.	0.	1.	0.	0.	1.4
5	Al Si Ca	0.	7.	53.	20.	0.	0.	0.	1.	16.	0.	1.	0.	1.	0.	0.	0.6
10	Al Fe Mg	0.	18.	35.	5.	0.	3.	1.	0.	8.	0.	24.	0.	7.	0.	0.	0.9
47	Al Mg Fe	0.	22.	43.	3.	1.	4.	1.	0.	8.	1.	13.	0.	3.	0.	0.	5.5
10	Fe Al Mg	0.	17.	25.	2.	0.	5.	0.	1.	9.	0.	37.	0.	2.	0.	0.	0.6
30	Mg Al Fe	1.	41.	29.	2.	0.	3.	0.	0.	9.	1.	12.	0.	3.	0.	0.	3.8
7	Al Ca Fe	0.	0.	62.	1.	0.	1.	1.	0.	18.	1.	10.	0.	5.	0.	0.	0.7
6	Al Fe Ca	0.	5.	60.	2.	0.	2.	0.	0.	15.	0.	16.	0.	0.	0.	0.	0.5
23	Al Mg Zn	0.	27.	41.	2.	0.	4.	1.	0.	5.	1.	6.	0.	12.	0.	0.	2.0
6	Al Zn Mg	0.	14.	45.	2.	0.	2.	0.	3.	9.	1.	7.	0.	17.	0.	0.	0.5
113	OTHERS -	3.	13.	31.	8.	0.	6.	2.	0.	11.	3.	17.	1.	6.	0.	0.	8.6

TABLE 4-68. - PSIT/SECV Loy Yang test 1 ash probe (ring 7) on filter untreated (Cont.)

147 ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE 7.0

1199 TOTALS - 1. 26. 29. 12. 0. 3. 1. 0. 13. 1. 10. 0. 3. 0. 0. 100.0

SAMPLE # 593 PSI Loy Yang test 1 ash probe (ring 7) on filter untreated

NUMBER 593 DISK 53 FILE 101 - 104 PARTICLES

RUN 1 DATE 15-JUL-91 SUMMARY 104 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Al Mg Ca	17.5	27.	40.	20.	12.	1.	0.	0.
Mg Ca Al	8.0	15.	62.	20.	2.	0.	0.	0.
Mg Al Ca	15.3	29.	47.	20.	4.	0.	0.	0.
Al Mg Fe	5.5	25.	59.	12.	4.	0.	0.	0.
OTHERS -	8.6	42.	23.	22.	13.	0.	0.	0.
OTHERS -	45.2	20.	32.	26.	13.	7.	3.	0.
TOTALS -	100.0	24.	39.	23.	10.	3.	1.	0.

**TABLE 4-69. - PSIT/SECV Loy Yang test 4 ash probe (horizontal duct)
untreated on filter**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 594 PSI Loy Yang test 4 ash probe (Horiz. duct) untreated on filter
NUMBER 594 DISK 53 FILE 105 - 108 PARTICLES
RUN 1 DATE 16-JUL-91 SUMMARY 108 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.18907E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
29	Fe - -	0.	2.	2.	1.	0.	0.	0.	0.	1.	0.	92.	0.	2.	0.	0.	1.7
103	Si - -	3.	0.	1.	95.	0.	0.	0.	0.	0.	0.	1.	0.	0.	0.	0.	7.1
9	Si Al -	0.	0.	14.	84.	0.	0.	1.	0.	0.	0.	0.	0.	0.	0.	0.	1.0
29	Si Na -	22.	0.	1.	71.	0.	0.	0.	0.	2.	0.	2.	0.	1.	0.	0.	2.5
14	Si Al Na	15.	2.	20.	53.	0.	0.	0.	0.	3.	1.	5.	0.	0.	0.	0.	0.8
71	Si Na Al	23.	1.	12.	56.	0.	0.	0.	0.	2.	1.	5.	0.	0.	0.	0.	5.5
13	Si Mg Ca	1.	26.	8.	38.	0.	1.	0.	0.	16.	0.	9.	0.	0.	0.	0.	1.3
26	Mg Ca Si	0.	44.	10.	16.	0.	0.	0.	0.	22.	0.	7.	0.	0.	0.	0.	1.8
25	Mg Si Ca	0.	40.	9.	26.	0.	0.	0.	0.	16.	0.	8.	0.	0.	0.	0.	1.7
12	Si Al Fe	2.	1.	19.	64.	0.	0.	0.	0.	3.	1.	10.	0.	0.	0.	0.	0.6
10	Si Fe Al	3.	5.	11.	54.	0.	0.	0.	0.	7.	3.	17.	0.	0.	0.	0.	0.5
6	Si Na Mg	21.	12.	10.	40.	0.	0.	0.	0.	9.	1.	7.	0.	0.	0.	0.	0.5
6	Si Mg Na	11.	19.	7.	48.	0.	0.	0.	0.	9.	2.	4.	0.	0.	0.	0.	0.7
10	Si Na Fe	24.	2.	4.	55.	0.	0.	1.	0.	3.	1.	11.	0.	1.	0.	0.	0.8
3	Mg Si Fe	0.	33.	10.	29.	0.	3.	0.	0.	10.	0.	13.	0.	2.	0.	0.	0.7
3	Al Ca Si	0.	17.	35.	21.	0.	0.	0.	0.	22.	0.	5.	0.	0.	0.	0.	0.6
15	Si Mg Al	1.	23.	18.	37.	0.	1.	0.	0.	11.	2.	7.	0.	1.	0.	0.	0.8
8	Si Al Mg	3.	14.	22.	44.	0.	0.	0.	0.	9.	1.	3.	0.	3.	0.	0.	1.0
25	Mg Si Al	0.	39.	16.	24.	0.	0.	0.	0.	13.	1.	7.	0.	0.	0.	0.	2.3
7	Al Si Mg	0.	20.	38.	21.	0.	0.	0.	0.	15.	0.	5.	0.	1.	0.	0.	1.2
28	Mg Al Si	0.	39.	22.	16.	0.	1.	1.	0.	12.	1.	6.	1.	1.	0.	0.	1.9
10	Mg Fe Ca	0.	52.	6.	2.	0.	2.	1.	0.	17.	0.	19.	0.	1.	0.	0.	0.6
30	Mg Ca Fe	0.	54.	5.	3.	0.	1.	0.	0.	26.	0.	11.	0.	0.	0.	0.	2.1
5	Fe Mg Ca	0.	21.	8.	7.	0.	1.	0.	0.	18.	0.	45.	0.	0.	0.	0.	1.0
83	Al Mg Ca	0.	27.	44.	4.	0.	2.	1.	1.	13.	0.	6.	0.	2.	0.	0.	8.2
62	Mg Ca Al	0.	50.	14.	4.	0.	1.	0.	0.	22.	0.	7.	0.	0.	0.	0.	5.5
140	Mg Al Ca	0.	44.	26.	4.	0.	2.	1.	0.	15.	0.	6.	0.	1.	0.	0.	11.9
17	Al Ca Mg	0.	18.	51.	2.	0.	2.	0.	0.	23.	0.	5.	0.	0.	0.	0.	2.5
35	Al Zn Mg	1.	16.	42.	2.	0.	4.	1.	0.	5.	1.	6.	0.	21.	0.	0.	3.1
28	Al Mg Zn	0.	23.	39.	7.	0.	2.	2.	0.	7.	1.	6.	0.	13.	0.	0.	3.0
36	Al Mg Fe	0.	26.	41.	2.	0.	4.	1.	1.	8.	1.	13.	0.	3.	0.	0.	3.8

TABLE 4-69. - PSIT/SECV Loy Yang test 4 ash probe (horizontal duct)
untreated on filter (Cont.)

9	Fe Al Mg	0.	15.	23.	7.	0.	1.	2.	1.	8.	0.	36.	0.	7.	0.	0.	1.2
25	Mg Al Fe	0.	43.	28.	3.	0.	1.	1.	0.	9.	1.	12.	0.	2.	0.	0.	1.7
3	Si Na Zn	13.	0.	0.	74.	0.	4.	0.	0.	2.	0.	0.	0.	7.	0.	0.	0.7
101	OTHERS -	1.	17.	23.	9.	0.	4.	2.	0.	13.	3.	17.	0.	10.	0.	0.	10.0
163	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.2
1199	TOTALS -	3.	23.	22.	23.	0.	2.	1.	0.	11.	1.	10.	0.	3.	0.	0.	100.0

SAMPLE # 594 PSI Loy Yang test 4 ash probe (Horiz. duct) untreated on filter
 NUMBER 594 DISK 53 FILE 105 - 108 PARTICLES
 RUN 1 DATE 16-JUL-91 SUMMARY 108 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>5000 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Si - -	7.1	0.	4.	9.	36.	33.	17.	0.
Si Na Al	5.5	8.	26.	13.	27.	23.	4.	0.
Al Mg Ca	8.2	22.	54.	19.	5.	1.	0.	0.
Mg Ca Al	5.5	12.	50.	31.	6.	0.	0.	0.
Mg Al Ca	11.9	36.	43.	17.	4.	0.	0.	0.
OTHERS -	10.0	31.	37.	13.	18.	0.	0.	0.
OTHERS -	51.8	20.	33.	22.	17.	7.	1.	0.
TOTALS -	100.0	21.	35.	19.	16.	7.	2.	0.

TABLE 4-70. - SECV/PSIT Loy Yang test #4 precipitator ash collected from electrostatic

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 599 SECV/PSI LOY YANG TEST #4 PRECIP. ASH COLLECTED FROM ELECTROSTATIC
 NUMBER 599 DISK 40 FILE 113 - 116 PARTICLES
 RUN 1 DATE 23-DEC-91 SUMMARY 116 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.23363E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
13	Fe - -	1.	1.	0.	0.	0.	1.	0.	0.	0.	0.	95.	0.	2.	0.	0.	0.9
7	Si - -	5.	0.	0.	90.	0.	0.	3.	0.	0.	0.	0.	0.	1.	0.	0.	0.5
34	Cl Na -	33.	1.	3.	0.	0.	2.	59.	0.	1.	0.	1.	0.	1.	0.	0.	3.2
64	Al Mg Zn	1.	22.	48.	1.	0.	4.	4.	0.	3.	1.	4.	0.	10.	0.	0.	5.2
12	Mg Al Zn	0.	37.	24.	1.	0.	5.	5.	0.	9.	1.	4.	0.	13.	0.	0.	1.1
4	Si Al Na	15.	8.	23.	38.	0.	0.	1.	0.	5.	0.	6.	0.	4.	0.	0.	0.5
14	Si Na Al	18.	3.	12.	53.	0.	1.	3.	0.	2.	0.	4.	0.	3.	0.	0.	1.3
16	Mg Al Cl	4.	37.	26.	1.	0.	5.	12.	0.	7.	0.	2.	0.	4.	0.	0.	0.9
69	Al Mg Cl	2.	22.	40.	1.	0.	5.	13.	1.	6.	0.	4.	0.	5.	0.	0.	6.1
37	Al Cl Mg	5.	15.	38.	1.	0.	5.	20.	1.	3.	1.	3.	0.	7.	0.	0.	3.3
11	Mg Cl Al	6.	35.	13.	2.	0.	6.	20.	0.	8.	1.	4.	1.	3.	0.	0.	1.0
14	Cl Al Mg	4.	16.	21.	3.	0.	10.	31.	0.	5.	0.	3.	0.	5.	0.	0.	1.8
26	Cl Na S	28.	5.	6.	1.	0.	15.	39.	0.	1.	0.	3.	0.	2.	0.	0.	3.1
7	Cl S Na	18.	10.	8.	2.	0.	22.	32.	1.	2.	0.	1.	0.	4.	0.	0.	0.5
11	Na Cl S	36.	3.	6.	1.	0.	16.	30.	0.	3.	1.	2.	0.	1.	0.	0.	0.9
62	Al Mg Ca	1.	26.	44.	2.	0.	4.	3.	1.	12.	0.	4.	0.	3.	0.	0.	5.3
38	Mg Al Ca	0.	39.	29.	4.	0.	3.	3.	0.	13.	0.	6.	0.	3.	0.	0.	3.2
13	Mg Ca Al	0.	46.	13.	4.	0.	3.	5.	0.	19.	0.	8.	0.	2.	0.	0.	1.7
17	S Na Mg	28.	13.	6.	0.	0.	43.	4.	0.	4.	0.	1.	0.	1.	0.	0.	1.1
15	S Mg Na	19.	25.	5.	1.	0.	40.	4.	1.	1.	0.	1.	0.	3.	0.	0.	1.1
52	Al Mg S	1.	24.	45.	1.	0.	12.	3.	0.	5.	1.	3.	1.	4.	0.	0.	4.2
20	Al S Mg	3.	17.	42.	1.	0.	20.	5.	1.	5.	0.	3.	0.	5.	0.	0.	2.1
10	S Mg Al	10.	22.	16.	1.	0.	31.	6.	1.	2.	3.	2.	0.	5.	0.	0.	0.8
20	Al Mg Fe	1.	22.	47.	1.	0.	5.	5.	1.	5.	0.	10.	0.	4.	0.	0.	1.8
4	Mg Ca Fe	0.	48.	2.	4.	0.	2.	1.	0.	32.	0.	10.	0.	1.	0.	0.	0.9
15	Al Cl Zn	5.	9.	34.	0.	0.	6.	23.	0.	3.	0.	3.	0.	15.	0.	0.	1.2
3	Zn Al Cl	11.	3.	20.	8.	1.	12.	15.	1.	0.	0.	4.	0.	24.	0.	0.	0.7
3	Cl S Mg	0.	20.	1.	0.	0.	30.	42.	6.	0.	0.	0.	0.	1.	0.	0.	1.0
20	Cl Al Na	17.	9.	23.	1.	0.	5.	33.	0.	3.	0.	2.	0.	6.	0.	0.	2.3
41	Cl Na Al	26.	5.	13.	1.	0.	4.	42.	0.	2.	0.	2.	0.	4.	0.	0.	4.2
11	Al Na Cl	19.	5.	42.	1.	0.	8.	14.	1.	4.	0.	3.	0.	4.	0.	0.	1.6

TABLE 4-70. - SECV/PSIT Loy Yang test #4 precipitator ash collected from electrostatic (Cont.)

13	Al Mg Si	0.	22.	43.	12.	0.	1.	2.	0.	6.	1.	5.	1.	6.	0.	0.	1.6
8	Cl Mg Na	16.	22.	8.	3.	0.	6.	32.	0.	7.	0.	4.	0.	2.	0.	0.	0.5
322	OTHERS -	13.	14.	20.	8.	0.	12.	12.	1.	6.	1.	5.	0.	7.	0.	0.	26.4
139	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																7.6
1165	TOTALS -	10.	17.	25.	5.	0.	10.	15.	1.	6.	1.	5.	0.	5.	0.	0.	100.0

SAMPLE # 599 SECV/PSI LOY YANG TEST #4 PRECIP. ASH COLLECTED FROM ELECTROSTATIC
NUMBER 599 DISK 40 FILE 113 - 116 PARTICLES
RUN 1 DATE 23-DEC-91 SUMMARY 116 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Al Mg Zn	5.2	24.	29.	27.	18.	1.	0.	0.
Al Mg Cl	6.1	8.	17.	40.	31.	4.	0.	0.
Al Mg Ca	5.3	14.	28.	27.	29.	2.	0.	0.
Al Mg S	4.2	29.	13.	41.	15.	1.	0.	0.
Cl Na Al	4.2	10.	40.	38.	12.	0.	0.	0.
OTHERS -	26.4	22.	21.	34.	23.	0.	0.	0.
OTHERS -	48.7	9.	25.	33.	29.	4.	0.	0.
TOTALS -	100.0	14.	24.	34.	26.	2.	0.	0.

TABLE 4-71. - SECV/PSIT Loy Yang test #1 precipitator ash from electrostatic precipitator pla

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 598 SECV/PSI LOY YANG TEST 1 PRECIP. ASH FROM ELECTROSTATIC PRECIP. PLA
 NUMBER 598 DISK 40 FILE 109 - 112 PARTICLES
 RUN 1 DATE 22-DEC-91 SUMMARY 112 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

TOTAL Volume FACTOR: 0.22598E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
21	Si - -	3.	0.	0.	94.	0.	0.	1.	0.	0.	1.	0.	0.	0.	0.	0.	1.2
44	Fe - -	1.	2.	1.	0.	0.	2.	1.	0.	1.	0.	92.	0.	0.	0.	0.	3.4
27	Al - -	2.	4.	67.	0.	0.	4.	4.	1.	7.	5.	5.	0.	1.	0.	0.	1.5
6	Ca S -	1.	0.	0.	0.	0.	31.	0.	0.	65.	0.	3.	0.	0.	0.	0.	0.7
12	Cl Na -	33.	0.	1.	0.	0.	0.	64.	0.	0.	0.	0.	0.	0.	0.	0.	0.9
8	Na S Cl	37.	2.	9.	1.	0.	25.	16.	1.	2.	1.	6.	0.	0.	0.	0.	1.3
3	S Na Cl	26.	3.	6.	2.	0.	32.	17.	6.	4.	1.	3.	0.	0.	0.	0.	0.7
6	Ca Si Fe	0.	3.	7.	19.	0.	0.	0.	0.	59.	0.	12.	0.	0.	0.	0.	0.8
7	Ca Fe Si	4.	2.	12.	16.	0.	3.	1.	0.	40.	0.	21.	0.	0.	0.	0.	1.2
76	Al Mg Ca	0.	19.	55.	1.	0.	6.	2.	1.	11.	1.	5.	0.	0.	0.	0.	6.0
16	Al Ca Mg	1.	11.	57.	0.	0.	7.	3.	1.	14.	0.	5.	0.	0.	0.	0.	1.6
30	Cl Na Al	29.	1.	16.	0.	0.	5.	41.	0.	4.	1.	4.	0.	0.	0.	0.	3.5
29	Al Na Cl	21.	6.	36.	0.	0.	9.	14.	1.	5.	3.	4.	0.	0.	0.	0.	2.9
18	Al Cl Na	19.	5.	31.	0.	0.	7.	23.	1.	5.	4.	5.	0.	0.	0.	0.	1.6
8	Cl Al Na	19.	6.	24.	0.	0.	11.	29.	1.	6.	1.	3.	0.	2.	0.	0.	0.7
7	Cl Na Fe	24.	1.	7.	0.	0.	4.	48.	0.	1.	0.	15.	0.	0.	0.	0.	0.9
10	Si Ca Al	3.	0.	22.	38.	0.	0.	0.	2.	29.	0.	5.	0.	0.	0.	0.	0.7
26	Ca Si Al	1.	1.	17.	24.	0.	1.	1.	0.	44.	1.	8.	0.	0.	0.	0.	2.1
9	Ca Al Si	0.	3.	18.	15.	0.	8.	4.	1.	40.	2.	9.	0.	0.	0.	0.	0.6
24	Al S Mg	3.	16.	45.	0.	0.	19.	4.	1.	7.	1.	3.	0.	0.	0.	0.	1.8
43	Al Mg S	0.	20.	52.	0.	0.	12.	1.	2.	6.	1.	5.	0.	0.	0.	0.	4.2
7	Ca S Fe	0.	0.	0.	0.	0.	30.	1.	0.	49.	0.	19.	0.	0.	0.	0.	0.5
21	Fe Ca Mg	0.	17.	2.	0.	0.	2.	0.	0.	29.	0.	50.	0.	0.	0.	0.	1.9
11	Al Cl S	0.	3.	56.	0.	0.	11.	17.	1.	4.	4.	3.	0.	1.	0.	0.	0.7
8	Al Fe Ca	6.	3.	48.	5.	0.	6.	1.	0.	11.	0.	19.	0.	0.	0.	0.	0.7
8	Al Ca Fe	3.	7.	52.	2.	0.	4.	1.	0.	16.	2.	12.	0.	0.	0.	0.	0.5
10	Na Al S	30.	6.	25.	0.	0.	17.	7.	1.	5.	2.	6.	0.	0.	0.	0.	1.4
10	Al S Na	17.	8.	39.	1.	0.	18.	1.	1.	11.	2.	2.	0.	0.	0.	0.	0.8
10	S Na Al	34.	1.	15.	0.	0.	37.	2.	2.	5.	1.	2.	0.	0.	0.	0.	1.1
37	Al Na S	23.	5.	39.	0.	0.	16.	3.	1.	5.	2.	5.	0.	0.	0.	0.	4.6

TABLE 4-71. - SECV/PSIT Loy Yang test #1 precipitator ash from electrostatic precipitator pla (Cont.)

4	Fe S Na	13.	0.	3.	0.	0.	13.	6.	0.	9.	0.	55.	0.	0.	0.	0.	0.5
7	S Na Fe	32.	2.	4.	1.	0.	37.	0.	2.	7.	0.	14.	0.	0.	0.	0.	0.5
6	Al Ti Cl	0.	1.	48.	1.	0.	2.	11.	0.	8.	21.	7.	0.	0.	0.	0.	0.6
9	Si Al Na	13.	2.	24.	49.	0.	3.	1.	1.	5.	2.	1.	0.	0.	0.	0.	0.6
10	Al Mg Cl	1.	19.	52.	0.	1.	7.	10.	0.	5.	3.	2.	0.	0.	0.	0.	1.6
16	Al Ti Ca	0.	2.	55.	1.	0.	3.	0.	0.	10.	22.	6.	0.	0.	0.	0.	2.3
5	Al Ca Ti	0.	1.	60.	0.	0.	3.	2.	0.	14.	12.	8.	0.	0.	0.	0.	1.0
11	Al Ti Fe	1.	4.	53.	0.	0.	2.	2.	1.	5.	21.	10.	0.	1.	0.	0.	0.6
31	Al Mg Fe	0.	18.	52.	0.	0.	7.	1.	1.	6.	1.	11.	0.	1.	0.	0.	2.1
18	Al S Ca	0.	4.	51.	0.	0.	19.	1.	1.	14.	3.	6.	0.	1.	0.	0.	0.7
354	OTHERS -	10.	9.	26.	8.	0.	10.	6.	1.	12.	3.	15.	0.	0.	0.	0.	30.6
154	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.1
1177	TOTALS -	10.	8.	30.	6.	0.	10.	7.	1.	11.	3.	13.	0.	0.	0.	0.	100.0

SAMPLE # 598 SECV/PSI LOY YANG TEST 1 PRECIP. ASH FROM ELECTROSTATIC PRECIP. PLA
NUMBER 598 DISK 40 FILE 109 - 112 PARTICLES
RUN 1 DATE 22-DEC-91 SUMMARY 112 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Al Mg Ca	6.0	27.	29.	26.	17.	1.	0.	0.
Al Na S	4.6	12.	67.	15.	6.	0.	0.	0.
Al Mg S	4.2	22.	43.	23.	12.	0.	0.	0.
OTHERS -	30.6	25.	37.	21.	16.	0.	0.	0.
OTHERS -	54.6	14.	35.	26.	21.	4.	0.	0.
TOTALS -	100.0	19.	37.	24.	18.	2.	0.	0.

**TABLE 4-72. - PSIT/SECV Loy Yang treated ash probe (horizontal duct)
test 3 on filter**

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 595 PSI Loy Yang treated ash probe (horiz. duct.) test 3 on filter

NUMBER 595 DISK 53 FILE 109 - 112 PARTICLES

RUN 1 DATE 17-JUL-91 SUMMARY 112 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.13048E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
32	Si - -	3.	0.	2.	93.	0.	0.	0.	0.	0.	1.	1.	0.	1.	0.	0.	3.5
19	Fe - -	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	96.	0.	3.	0.	0.	1.3
4	Ti - -	0.	3.	5.	0.	0.	0.	0.	0.	3.	86.	1.	0.	3.	0.	0.	0.5
15	Zn Al -	0.	0.	32.	0.	0.	0.	0.	0.	0.	0.	0.	1.	67.	0.	0.	1.0
15	S Al Zn	1.	3.	25.	4.	0.	40.	6.	0.	1.	0.	1.	0.	18.	0.	0.	1.2
10	S Zn Al	2.	2.	19.	0.	0.	44.	1.	0.	2.	0.	1.	0.	29.	0.	0.	0.9
12	Al S Zn	4.	4.	42.	0.	0.	24.	3.	0.	5.	0.	1.	0.	17.	0.	0.	0.8
52	Al Zn S	1.	2.	51.	1.	0.	13.	0.	1.	3.	2.	3.	0.	23.	0.	0.	4.6
14	Zn Al S	0.	1.	31.	1.	1.	12.	1.	1.	3.	0.	4.	0.	44.	0.	0.	0.9
10	Si Al Zn	4.	2.	27.	47.	0.	1.	0.	0.	4.	0.	3.	0.	12.	0.	0.	0.9
68	Al Zn Si	0.	6.	44.	13.	0.	2.	0.	0.	4.	1.	5.	0.	24.	0.	0.	5.9
25	Al Si Zn	0.	6.	47.	20.	0.	1.	0.	0.	6.	1.	5.	0.	15.	0.	0.	2.0
6	S Al Mg	0.	20.	24.	5.	4.	34.	1.	0.	0.	0.	0.	0.	11.	0.	0.	0.9
3	Al S Mg	8.	20.	30.	4.	0.	23.	0.	0.	3.	1.	0.	3.	9.	0.	0.	0.5
6	Al Mg S	0.	25.	49.	0.	0.	11.	5.	0.	0.	0.	7.	0.	2.	0.	0.	0.9
6	S Cl Al	0.	0.	21.	4.	0.	36.	27.	2.	0.	4.	2.	0.	4.	0.	0.	0.5
9	S Al Cl	0.	2.	27.	3.	0.	38.	17.	3.	2.	0.	0.	5.	2.	0.	0.	0.7
4	Al S Cl	0.	0.	37.	1.	0.	28.	18.	0.	10.	1.	0.	1.	3.	0.	0.	0.6
6	Si Ca Al	5.	0.	21.	38.	0.	2.	0.	1.	25.	1.	7.	0.	0.	0.	0.	0.5
6	Ca Si Al	0.	0.	19.	27.	0.	1.	0.	0.	43.	0.	10.	0.	0.	0.	0.	0.7
23	Al Mg Fe	0.	22.	45.	1.	0.	4.	0.	0.	8.	1.	13.	0.	6.	0.	0.	1.9
10	Al Fe Mg	0.	16.	42.	3.	0.	0.	0.	0.	4.	0.	26.	0.	8.	0.	0.	1.5
5	Si Na Al	12.	2.	9.	72.	0.	0.	0.	1.	0.	0.	1.	0.	1.	0.	0.	0.5
5	Si Al Na	17.	2.	29.	37.	0.	0.	0.	0.	3.	7.	3.	0.	2.	0.	0.	0.6
26	Al Zn Ca	0.	2.	55.	3.	0.	2.	1.	0.	10.	0.	4.	0.	24.	0.	0.	2.2
28	Zn Al Fe	0.	1.	31.	1.	0.	3.	0.	1.	2.	1.	11.	0.	48.	0.	0.	1.5
72	Al Zn Fe	0.	2.	49.	3.	0.	2.	0.	1.	4.	1.	12.	0.	26.	0.	0.	5.1
12	Al Fe Zn	0.	8.	43.	2.	0.	2.	1.	0.	5.	2.	22.	0.	14.	0.	0.	0.5
31	Zn Al Mg	0.	16.	30.	2.	0.	1.	2.	0.	2.	1.	6.	0.	40.	0.	0.	2.1
115	Al Mg Zn	0.	23.	46.	2.	0.	2.	0.	0.	4.	1.	5.	0.	15.	0.	0.	10.1
162	Al Zn Mg	0.	16.	44.	4.	0.	3.	0.	0.	4.	1.	4.	0.	24.	0.	0.	12.6
10	Al Mg Si	0.	22.	48.	11.	0.	0.	0.	0.	7.	1.	5.	0.	7.	0.	0.	0.7
5	Si Al Mg	0.	14.	31.	41.	0.	0.	0.	0.	5.	0.	4.	0.	5.	0.	0.	0.5

TABLE 4-72. - PSIT/SECV Loy Yang treated ash probe (horizontal duct)
test 3 on filter (Cont.)

16	Al Si Mg	0.	14.	45.	22.	0.	0.	0.	0.	6.	1.	6.	0.	5.	0.	0.	1.6
11	Al Ti Mg	0.	14.	43.	3.	1.	2.	1.	1.	4.	22.	5.	0.	5.	0.	0.	0.9
8	Al Mg Ti	0.	21.	47.	2.	0.	0.	0.	0.	4.	12.	5.	0.	8.	0.	0.	0.9
15	Al Zn Ti	0.	2.	50.	3.	0.	2.	0.	0.	1.	14.	2.	0.	24.	0.	0.	1.1
6	Al Zn Cl	0.	0.	51.	1.	0.	7.	12.	0.	0.	0.	1.	6.	22.	0.	0.	0.5
5	Al Ca Mg	0.	10.	51.	1.	0.	4.	2.	0.	16.	4.	5.	0.	8.	0.	0.	0.9
10	Al Mg Ca	0.	26.	46.	2.	0.	2.	2.	0.	10.	1.	4.	1.	4.	0.	0.	1.6
14	Si Zn Na	13.	0.	3.	58.	0.	1.	0.	0.	0.	0.	1.	0.	24.	0.	0.	1.5
166	OTHERS -	4.	4.	26.	9.	1.	6.	4.	4.	6.	3.	13.	0.	19.	0.	0.	13.6
121	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.0
198	TOTALS -	2.	9.	36.	11.	0.	6.	2.	1.	5.	3.	8.	0.	18.	0.	0.	100.0

SAMPLE # 595 PSI Loy Yang treated ash probe (horiz. duct.) test 3 on filter
NUMBER 595 DISK 53 FILE 109 - 112 PARTICLES
RUN 1 DATE 17-JUL-91 SUMMARY 112 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Al Mg Zn	10.1	13.	35.	39.	13.	0.	0.	0.
Al Zn Mg	12.6	27.	28.	36.	9.	0.	0.	0.
Al Zn S	4.6	22.	32.	38.	9.	0.	0.	0.
Al Zn Si	5.9	30.	36.	28.	6.	0.	0.	0.
Al Zn Fe	5.1	27.	25.	39.	9.	0.	0.	0.
OTHERS -	13.6	32.	22.	28.	19.	0.	0.	0.
OTHERS -	48.0	18.	18.	28.	24.	9.	3.	0.
TOTALS -	100.0	22.	23.	31.	18.	4.	2.	0.

TABLE 4-73. - SECV/PSIT Loy Yang treated precipitator ash collected from electrostatic

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 600 SECV/PSI LOY YANG TREATED PRECIP. ASH COLLECTED FROM ELECTROSTATIC
 NUMBER 600 DISK 40 FILE 117 - 120 PARTICLES
 RUN 1 DATE 24-DEC-91 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>50UU 0

TOTAL Volume FACTOR: 0.21052E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
15	Al Mg	0.	31.	56.	0.	0.	1.	3.	0.	2.	0.	2.	1.	2.	0.	0.	1.7
253	Al Mg Zn	1.	25.	43.	1.	0.	5.	4.	0.	3.	1.	4.	0.	13.	0.	0.	20.2
199	Al Zn Mg	1.	16.	39.	2.	0.	5.	4.	0.	3.	1.	5.	0.	24.	0.	0.	17.3
97	Zn Al Mg	1.	14.	27.	2.	0.	5.	5.	0.	2.	1.	4.	0.	37.	0.	0.	8.3
15	Mg Al Zn	1.	40.	30.	1.	0.	5.	3.	0.	3.	0.	2.	0.	15.	0.	0.	0.7
36	Al Zn Cl	1.	7.	39.	1.	0.	5.	13.	0.	2.	0.	2.	0.	29.	0.	0.	4.3
5	Al Cl Zn	2.	10.	34.	0.	0.	8.	21.	2.	3.	0.	2.	0.	17.	0.	0.	0.5
58	Zn Al Cl	2.	7.	21.	0.	0.	7.	13.	1.	1.	0.	3.	0.	44.	0.	0.	5.7
28	Zn Cl Al	2.	7.	14.	0.	1.	10.	19.	0.	1.	0.	2.	0.	45.	0.	0.	3.1
11	Al Mg Cl	0.	26.	45.	0.	0.	6.	12.	4.	2.	0.	1.	0.	3.	0.	0.	1.0
4	Mg Al Cl	4.	36.	25.	0.	0.	4.	12.	0.	6.	0.	4.	0.	9.	0.	0.	1.1
14	Al Mg Ti	1.	25.	48.	2.	0.	1.	0.	1.	4.	10.	3.	1.	4.	0.	0.	0.9
14	Al Mg Fe	0.	27.	46.	1.	0.	4.	2.	0.	2.	1.	12.	1.	4.	0.	0.	0.9
4	Fe Al Mg	0.	14.	27.	0.	2.	7.	0.	0.	8.	0.	33.	0.	9.	0.	0.	0.6
37	Al Mg S	1.	28.	44.	1.	0.	9.	2.	1.	4.	1.	2.	0.	6.	0.	0.	2.4
5	Al S Mg	10.	15.	34.	1.	0.	18.	2.	0.	7.	2.	3.	0.	8.	0.	0.	0.5
11	Al Mg Si	2.	21.	44.	14.	0.	1.	1.	1.	4.	1.	3.	0.	7.	0.	0.	0.9
6	Al Si Mg	3.	17.	36.	22.	0.	0.	0.	0.	6.	2.	7.	0.	5.	0.	0.	0.8
14	Al Mg Ca	0.	28.	47.	0.	0.	3.	2.	0.	10.	0.	5.	0.	4.	0.	0.	0.9
28	Zn Al S	2.	6.	21.	1.	0.	12.	6.	0.	2.	1.	3.	0.	46.	0.	0.	2.4
20	Al Zn S	2.	6.	36.	0.	1.	15.	6.	2.	4.	1.	3.	0.	24.	0.	0.	1.6
11	Zn S Al	3.	9.	15.	1.	2.	17.	9.	0.	4.	0.	2.	0.	37.	0.	0.	1.0
20	Al Mg Na	13.	23.	41.	0.	0.	6.	3.	0.	3.	1.	3.	0.	6.	0.	0.	1.2
24	Zn Cl S	1.	2.	5.	1.	0.	14.	21.	0.	1.	0.	1.	0.	52.	0.	0.	2.8
1	Al S Na	17.	0.	32.	0.	0.	23.	6.	0.	4.	0.	3.	0.	15.	0.	0.	0.5
11	Al Zn Na	15.	6.	38.	0.	1.	4.	6.	2.	1.	0.	3.	0.	24.	0.	0.	0.9
17	Zn Al Na	15.	0.	21.	1.	0.	6.	6.	1.	1.	0.	2.	0.	41.	0.	0.	1.2
8	Zn Al Fe	0.	7.	25.	1.	0.	4.	2.	0.	3.	0.	15.	0.	43.	0.	0.	1.0
4	Zn Fe Al	0.	9.	22.	0.	0.	2.	0.	0.	0.	2.	26.	0.	38.	0.	0.	0.8

TABLE 4-73. - SECV/PSIT Loy Yang treated precipitator ash collected from electrostatic (Cont.)

50	OTHERS -	15.	6.	11.	10.	0.	7.	20.	4.	3.	1.	1.	0.	21.	0.	0.	4.4
159	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																10.6
1180	TOTALS -	3.	15.	32.	3.	0.	6.	7.	1.	3.	1.	4.	0.	24.	0.	0.	100.0

SAMPLE # 600 SECV/PSI LOY YANG TREATED PRECIP. ASH COLLECTED FROM ELECTROSTATIC
 NUMBER 600 DISK 40 FILE 117 - 120 PARTICLES
 RUN 1 DATE 24-DEC-91 SUMMARY 120 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 16.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Al Mg Zn	20.2	11.	12.	28.	45.	5.	0.	0.
Al Zn Mg	17.3	10.	26.	32.	30.	2.	0.	0.
Zn Al Mg	8.3	31.	28.	26.	15.	0.	0.	0.
Al Zn Cl	4.3	6.	42.	18.	32.	2.	0.	0.
Zn Al Cl	5.7	20.	40.	30.	11.	0.	0.	0.
OTHERS -	4.4	45.	55.	0.	0.	0.	0.	0.
OTHERS -	39.8	18.	29.	29.	22.	2.	0.	0.
TOTALS -	100.0	17.	27.	27.	26.	2.	0.	0.

TABLE 4-74. - PSIT Beulah ash w/o ion exchange, 1s RST, (Coal #392)

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 548 PSI Beulah ash w/o ion exchange, 1 sec. RST, (COAL #392)

NUMBER 548 DISK 50 FILE 117 - 120 PARTICLES

RUN 1 DATE 18-JUN-91 SUMMARY 120 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.21974E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
16	Fe - -	0.	0.	1.	2.	0.	1.	0.	0.	3.	1.	92.	0.	0.	0.	0.	1.0
26	Si - -	0.	0.	0.	96.	0.	0.	0.	1.	1.	0.	0.	0.	0.	0.	0.	2.5
35	Ca - -	0.	5.	5.	4.	0.	4.	0.	0.	79.	1.	2.	0.	0.	0.	0.	3.5
14	Al - -	0.	0.	73.	1.	0.	9.	14.	0.	2.	1.	0.	0.	0.	0.	0.	1.0
36	Ca S -	0.	0.	0.	1.	0.	40.	0.	0.	59.	0.	0.	0.	0.	0.	0.	4.1
8	Fe Ca -	0.	0.	1.	1.	0.	0.	0.	0.	18.	0.	79.	0.	0.	0.	0.	0.6
43	Si Al -	0.	0.	43.	54.	0.	1.	0.	0.	1.	0.	0.	0.	0.	0.	0.	3.2
8	Ca Al -	0.	0.	18.	2.	0.	0.	0.	0.	78.	0.	1.	0.	1.	0.	0.	0.6
11	Ca Mg -	0.	13.	1.	1.	0.	3.	2.	0.	79.	0.	1.	0.	0.	0.	0.	1.3
10	Al Si Ca	4.	0.	41.	38.	0.	0.	0.	1.	17.	0.	0.	0.	0.	0.	0.	0.5
327	Ca Si Al	1.	2.	17.	22.	0.	2.	0.	0.	51.	1.	3.	0.	0.	0.	0.	27.8
92	Si Al Ca	2.	0.	32.	45.	0.	1.	0.	0.	17.	1.	1.	0.	0.	0.	0.	7.6
80	Ca Al Si	0.	3.	18.	14.	0.	3.	0.	0.	57.	1.	3.	0.	1.	0.	0.	5.7
44	Si Ca Al	6.	0.	23.	38.	0.	2.	0.	0.	28.	1.	1.	0.	0.	0.	0.	2.6
50	Si Al Na	20.	0.	32.	41.	0.	0.	0.	1.	5.	0.	0.	0.	0.	0.	0.	5.4
11	Na Si Al	36.	0.	23.	29.	0.	2.	1.	1.	8.	0.	0.	0.	0.	0.	0.	0.7
13	Si Na Al	30.	0.	23.	37.	0.	0.	0.	1.	7.	1.	0.	0.	0.	0.	0.	1.2
18	Ca S Al	1.	4.	12.	6.	0.	18.	0.	2.	53.	0.	2.	0.	2.	0.	0.	1.9
8	Ca Al S	0.	0.	18.	7.	0.	11.	0.	0.	61.	2.	0.	0.	0.	0.	0.	0.7
8	Si Al K	0.	0.	34.	45.	0.	1.	0.	17.	3.	0.	0.	0.	0.	0.	0.	0.6
27	Ca S Mg	0.	11.	3.	3.	0.	17.	0.	0.	52.	0.	2.	0.	0.	0.	0.	2.7
16	Ca Mg S	0.	16.	4.	3.	0.	11.	0.	0.	52.	0.	3.	0.	1.	0.	0.	2.2
21	Ca Al Mg	0.	11.	14.	5.	0.	3.	0.	0.	54.	1.	2.	1.	0.	0.	0.	1.7
23	Ca Mg Al	0.	14.	10.	4.	0.	3.	0.	0.	57.	2.	4.	0.	0.	0.	0.	2.3
12	Ca Si Fe	0.	3.	10.	19.	0.	2.	0.	0.	57.	2.	13.	0.	0.	0.	0.	0.7
12	Ca Fe Si	0.	2.	8.	12.	0.	4.	0.	0.	57.	2.	21.	1.	0.	0.	0.	0.7
29	Ca S Si	0.	2.	5.	13.	0.	25.	0.	0.	57.	2.	1.	1.	0.	0.	0.	2.7
18	Ca Si S	0.	2.	9.	18.	0.	13.	0.	0.	52.	2.	3.	0.	1.	0.	0.	1.8
8	Ca S Ti	0.	0.	7.	10.	0.	19.	1.	0.	50.	13.	0.	0.	0.	0.	0.	0.7
7	Ca Si Mg	0.	9.	4.	20.	0.	2.	1.	0.	62.	0.	2.	0.	0.	0.	0.	1.0

TABLE 4-74. - PSIT Beulah ash w/o ion exchange, 1s RST.
(Coal #392) (Cont.)

8	Ca Mg Si	0.	16.	4.	10.	0.	3.	0.	0.	67.	0.	0.	0.	0.	0.	0.6
4	Ca Si Na	15.	0.	11.	29.	0.	1.	0.	1.	37.	2.	3.	0.	0.	0.	0.6
16	OTHERS -	4.	4.	14.	27.	0.	6.	0.	0.	22.	5.	17.	0.	1.	0.	1.2
136	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE															8.4
1198	TOTALS -	3.	3.	16.	23.	0.	6.	0.	1.	41.	2.	4.	0.	0.	0.	99.8

SAMPLE # 548 PSI Beulah ash w/o ion exchange, 1 sec. RST, (COAL #392)
NUMBER 548 DISK 50 FILE 117 - 120 PARTICLES
RUN 1 DATE 18-JUN-91 SUMMARY 120 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>5000 0

VOLUME DISTRIBUTION

SPECIES	VOLUME %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 80.	80.-500.
Ca S -	4.1	5.	28.	26.	37.	3.	0.	0.
Si Al Na	5.4	42.	38.	16.	2.	2.	0.	0.
Ca Si Al	27.8	18.	30.	36.	14.	2.	1.	0.
Si Al Ca	7.6	23.	20.	32.	18.	6.	0.	0.
Ca Al Si	5.7	28.	29.	39.	3.	2.	0.	0.
OTHERS -	49.3	23.	19.	35.	19.	4.	1.	0.
TOTALS -	99.8	22.	24.	34.	16.	3.	1.	0.

TABLE 4-75. - PSIT Beulah ash, w/o ion exchange, 3s RST, (Coal #392)

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 549 PSI Beulah ash, w/o ion exchange, 3 sec. RST (COAL #392)
 NUMBER 549 DISK 50 FILE 121 - 126 PARTICLES
 RUN 1 DATE 18-JUN-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.16817E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
88	Ca - -	0.	1.	2.	3.	0.	1.	0.	0.	91.	0.	1.	0.	0.	0.	0.	8.4
17	Fe - -	0.	0.	0.	3.	0.	0.	0.	0.	1.	2.	95.	0.	0.	0.	0.	2.0
29	Si - -	4.	0.	0.	95.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	0.	1.4
9	Si Al -	0.	0.	45.	52.	0.	0.	0.	0.	2.	0.	0.	0.	0.	0.	0.	0.7
15	Ca Mg -	0.	16.	4.	3.	0.	1.	0.	0.	72.	1.	3.	0.	0.	0.	0.	2.1
26	Si Na -	18.	0.	0.	80.	0.	0.	0.	0.	1.	1.	0.	0.	0.	0.	0.	0.6
384	Ca Si Al	1.	3.	17.	24.	0.	0.	0.	0.	51.	1.	3.	0.	0.	0.	0.	34.2
63	Ca Al Si	0.	3.	19.	16.	0.	0.	0.	0.	56.	1.	3.	0.	0.	0.	0.	4.6
7	Al Si Ca	0.	0.	43.	39.	0.	0.	0.	2.	15.	1.	1.	0.	0.	0.	0.	0.6
64	Si Al Ca	8.	0.	30.	38.	0.	0.	0.	0.	19.	1.	2.	0.	0.	0.	0.	6.4
48	Si Ca Al	5.	0.	23.	35.	0.	1.	0.	0.	31.	2.	1.	0.	0.	0.	0.	4.4
134	Si Al Na	23.	0.	31.	39.	0.	0.	0.	0.	6.	0.	0.	0.	0.	0.	0.	11.2
44	Si Na Al	30.	0.	27.	37.	0.	0.	0.	0.	5.	0.	1.	0.	0.	0.	0.	4.7
15	Si Ca Na	13.	0.	6.	50.	0.	0.	0.	0.	25.	4.	0.	0.	0.	0.	0.	1.4
10	Si Na Ca	18.	0.	0.	72.	0.	0.	0.	0.	8.	0.	1.	0.	0.	0.	0.	1.2
28	Ca Si Mg	0.	10.	6.	15.	0.	1.	0.	0.	64.	1.	3.	0.	0.	0.	0.	1.7
27	Ca Mg Si	0.	15.	8.	11.	0.	0.	0.	0.	64.	0.	2.	0.	0.	0.	0.	2.2
2	Ti Ca Si	0.	0.	5.	14.	0.	0.	0.	0.	30.	50.	0.	0.	0.	0.	0.	0.8
22	Ca Mg Al	0.	15.	9.	3.	0.	0.	0.	0.	71.	1.	1.	0.	0.	0.	0.	1.4
17	Ca Al Mg	0.	10.	14.	6.	0.	0.	0.	0.	67.	0.	3.	0.	0.	0.	0.	1.7
9	Ca Fe Si	0.	5.	8.	11.	0.	0.	0.	0.	61.	0.	15.	0.	0.	0.	0.	0.5
7	Ca Si Fe	0.	4.	6.	16.	0.	0.	0.	0.	62.	2.	9.	0.	0.	0.	0.	0.6
128	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																6.4
1197	TOTALS -	6.	3.	17.	26.	0.	1.	0.	0.	42.	2.	4.	0.	0.	0.	0.	99.8

**TABLE 4-75. - PSIT Beulah ash, w/o ion exchange, 3s RST.
(Coal #392) (Cont.)**

SAMPLE # 549 PSI Beulah ash, w/o ion exchange, 3 sec. RST (COAL #392)
 NUMBER 549 DISK 50 FILE 121 - 124 PARTICLES
 RUN 1 DATE 18-JUN-91 SUMMARY 124 TOTAL 1199
 BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.-20.	20.-40.	40.-80.	80.-500.
Ca - -	8.4	5.	65.	12.	12.	6.	0.	0.
Ca Si Al	34.2	39.	45.	12.	3.	1.	0.	0.
Ca Al Si	4.6	33.	46.	15.	5.	0.	0.	0.
Si Al Ca	6.4	29.	41.	9.	8.	5.	8.	0.
Si Ca Al	4.4	42.	33.	8.	5.	1.	0.	10.
Si Al Na	11.2	29.	46.	12.	7.	5.	1.	0.
Si Na Al	4.7	55.	37.	5.	3.	0.	0.	0.
OTHERS -	25.9	21.	42.	14.	11.	7.	4.	0.
TOTALS -	99.8	30.	45.	12.	7.	4.	2.	0.

TABLE 4-76. - PSIT Beulah ash, WITH ion exchange, 1s RST. (Coal #392)

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 550 PSI Beulah ash, WITH ion exchange, 1 sec. RST (COAL # 392)

NUMBER 550 DISK 50 FILE 125 - 128 PARTICLES

RUN 1 DATE 20-JUN-91 SUMMARY 128 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.71439E+06

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
27	Si - -	0.	0.	1.	94.	0.	0.	0.	3.	1.	0.	0.	0.	0.	0.	0.	2.1
40	Ca - -	0.	4.	5.	3.	0.	3.	1.	2.	76.	1.	4.	0.	0.	0.	0.	4.2
13	Fe - -	0.	0.	0.	0.	0.	0.	1.	1.	0.	0.	97.	0.	0.	0.	0.	1.0
9	Si Al -	0.	0.	40.	55.	0.	1.	0.	2.	1.	1.	0.	0.	0.	0.	0.	0.5
29	K S -	0.	0.	0.	0.	0.	30.	0.	67.	1.	0.	0.	0.	0.	0.	0.	2.2
4	Si K -	0.	0.	0.	85.	0.	0.	0.	14.	1.	0.	0.	0.	0.	0.	0.	0.5
18	Si Ca K	0.	0.	8.	47.	0.	2.	0.	16.	24.	1.	1.	0.	1.	0.	0.	1.9
57	Ca K Si	0.	1.	11.	16.	0.	7.	0.	22.	38.	1.	3.	0.	0.	0.	0.	5.3
58	Ca Si K	0.	0.	13.	23.	0.	5.	0.	18.	36.	1.	3.	0.	0.	0.	0.	5.1
13	K Si Ca	0.	0.	18.	25.	0.	3.	0.	30.	22.	0.	1.	0.	2.	0.	0.	0.9
26	K Ca Si	0.	0.	13.	19.	0.	11.	0.	29.	24.	1.	2.	0.	0.	0.	0.	3.8
13	Si K Ca	0.	0.	13.	40.	0.	5.	1.	21.	16.	0.	0.	0.	4.	0.	0.	1.1
42	Ca Al Si	0.	2.	18.	15.	0.	3.	0.	6.	50.	1.	6.	0.	0.	0.	0.	2.3
18	Si Al Ca	0.	1.	28.	37.	0.	2.	0.	11.	18.	0.	2.	0.	0.	0.	0.	1.1
166	Ca Si Al	0.	1.	17.	21.	0.	2.	0.	8.	45.	1.	4.	0.	0.	0.	0.	14.1
14	Si Ca Al	0.	0.	19.	36.	0.	4.	1.	13.	23.	1.	0.	0.	1.	0.	0.	1.0
10	Al Si K	0.	0.	36.	31.	0.	1.	0.	22.	8.	0.	0.	0.	1.	0.	0.	0.8
82	Si Al K	0.	0.	35.	41.	0.	1.	0.	17.	5.	0.	0.	0.	0.	0.	0.	6.8
5	K Al Si	0.	0.	28.	25.	0.	1.	1.	37.	6.	0.	1.	0.	1.	0.	0.	0.5
47	K Si Al	0.	0.	24.	29.	0.	1.	0.	35.	9.	0.	0.	0.	0.	0.	0.	3.1
32	Si K Al	0.	0.	25.	35.	0.	3.	0.	28.	8.	0.	0.	0.	0.	0.	0.	2.5
4	K Cl P	0.	0.	0.	0.	14.	0.	23.	54.	5.	0.	0.	2.	3.	0.	0.	0.5
110	Ca K S	0.	2.	6.	12.	0.	16.	1.	22.	43.	1.	2.	0.	0.	0.	0.	10.3
26	K Ca S	0.	0.	8.	8.	0.	17.	0.	39.	15.	1.	1.	0.	1.	0.	0.	3.4
6	S K Ca	0.	0.	1.	7.	3.	35.	2.	28.	12.	1.	0.	0.	0.	0.	0.	0.8
49	Ca S K	0.	2.	5.	5.	0.	20.	0.	15.	43.	1.	2.	0.	0.	0.	0.	3.8
26	K S Ca	1.	0.	3.	4.	0.	27.	2.	43.	17.	1.	1.	0.	1.	0.	0.	1.5
11	Ca K Fe	0.	0.	5.	4.	0.	3.	1.	15.	59.	1.	10.	0.	0.	0.	0.	0.6
17	Ca K Al	0.	0.	17.	13.	0.	6.	0.	21.	15.	2.	2.	1.	1.	0.	0.	0.9
13	Ca Al K	0.	1.	20.	9.	0.	3.	0.	14.	47.	2.	3.	0.	1.	0.	0.	1.0
8	Ca Al Fe	0.	3.	15.	2.	0.	0.	0.	1.	58.	3.	8.	0.	0.	0.	0.	0.7
12	Ca Mg Al	0.	18.	11.	2.	0.	0.	0.	1.	53.	1.	5.	0.	0.	0.	0.	0.5
5	Ca Al Mg	0.	11.	13.	3.	0.	0.	0.	0.	53.	1.	7.	0.	0.	0.	0.	0.5

TABLE 4-76. - PSIT Beulah ash, WITH ion exchange, 1s RST,
(Coal #392) (Cont.)

10	Ca S Si	0.	1.	7.	12.	0.	24.	0.	9.	41.	2.	4.	0.	0.	0.	0.	0.8
6	Ca Si S	0.	1.	11.	20.	0.	15.	0.	11.	39.	1.	2.	0.	0.	0.	0.	0.5
5	K Ca Cl	0.	0.	5.	3.	0.	9.	13.	37.	30.	1.	0.	1.	0.	0.	0.	0.5
6	K S Si	0.	0.	4.	10.	0.	23.	0.	59.	3.	0.	0.	0.	0.	0.	0.	0.8
45	OTHERS -	2.	4.	13.	10.	0.	10.	1.	8.	37.	4.	10.	0.	1.	0.	0.	2.6
114	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																9.5
1196	TOTALS -	0.	1.	13.	20.	0.	8.	1.	19.	32.	1.	4.	0.	0.	0.	0.	100.0

SAMPLE # 550 PSI Beulah ash, WITH ion exchange, 1 sec. RST (COAL # 392)
NUMBER 550 DISK 50 FILE 125 - 128 PARTICLES
RUN 1 DATE 20-JUN-91 SUMMARY 128 TOTAL 1199
BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

Volume DISTRIBUTION

SPECIES	Volume %	0.0-2.5	2.5-5.0	5.0-10.	10.- 20.	20.- 40.	40.- 60.	60.-500.
Ca - -	4.2	6.	33.	21.	28.	12.	0.	0.
C- K Si	5.3	6.	8.	30.	45.	11.	0.	0.
Ca Si K	5.1	6.	28.	29.	23.	15.	0.	0.
Ca Si Al	14.1	20.	43.	16.	16.	3.	1.	0.
Si Al K	6.8	26.	32.	12.	21.	6.	3.	0.
Ca K S	10.3	7.	19.	38.	34.	3.	0.	0.
OTHERS -	54.1	17.	27.	2.	20.	9.	3.	0.
TOTALS -	100.0	15.	28.	2.	23.	8.	2.	0.

TABLE 4-77. - PSIT Beulah ash WITH ion exchange, 3s RST (Coal #392)

THIS DATA IS MODIFIED : CATEGORIES WITH VOLUME % LESS THAN 0.5 ARE PRINTED AS ONE CATEGORY

SAMPLE # 551 PSI Beulah ash WITH ion exchange, 3 sec. RST., (COAL # 392)

NUMBER 551 DISK 50 FILE 129 - 132 PARTICLES

RUN 1 DATE 25-JUN-91 SUMMARY 132 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

TOTAL Volume FACTOR: 0.19307E+07

AVERAGE SPECIES COMPOSITION

#	SPECIES	Na	Mg	Al	Si	P	S	Cl	K	Ca	Ti	Fe	Cu	Zn	Ba	X	Volume %
48	Ca - -	0.	6.	5.	5.	0.	0.	0.	0.	77.	1.	5.	0.	0.	0.	0.	3.4
24	Fe - -	0.	0.	1.	1.	0.	0.	0.	2.	1.	0.	95.	0.	0.	0.	0.	1.5
7	Si - -	0.	0.	0.	95.	0.	0.	0.	2.	2.	0.	0.	0.	1.	0.	0.	0.6
24	Si K -	0.	0.	0.	79.	0.	0.	0.	20.	1.	0.	0.	0.	0.	0.	0.	1.7
17	Si Al -	0.	0.	41.	56.	0.	0.	0.	2.	1.	0.	0.	0.	0.	0.	0.	2.5
178	K Si Al	0.	0.	24.	30.	0.	2.	0.	41.	3.	0.	0.	0.	0.	0.	0.	14.7
43	Si Al K	0.	0.	31.	38.	0.	1.	0.	20.	9.	0.	0.	0.	0.	0.	0.	4.0
39	Si K Al	0.	0.	24.	35.	0.	1.	0.	29.	9.	0.	1.	0.	0.	0.	0.	2.8
6	K Al Si	0.	0.	25.	23.	0.	5.	0.	36.	9.	0.	2.	0.	0.	0.	0.	0.5
5	Al K Si	0.	0.	30.	25.	0.	5.	0.	27.	9.	3.	1.	0.	1.	0.	0.	0.6
238	Ca Si Al	0.	1.	17.	22.	0.	1.	0.	6.	47.	1.	3.	0.	0.	0.	0.	20.2
20	Si Al Ca	0.	0.	26.	33.	0.	2.	1.	16.	20.	0.	2.	0.	0.	0.	0.	1.9
28	Si Ca Al	0.	0.	22.	31.	0.	3.	0.	15.	25.	1.	2.	0.	0.	0.	0.	2.0
46	Ca Al Si	0.	0.	23.	19.	0.	6.	0.	8.	40.	1.	3.	0.	0.	0.	0.	4.6
7	Al Si Ca	0.	0.	34.	30.	0.	6.	0.	10.	18.	1.	1.	0.	0.	0.	0.	0.5
33	Ca K Si	0.	1.	8.	16.	0.	10.	0.	26.	34.	1.	2.	0.	1.	0.	0.	2.8
30	Ca Si K	0.	1.	12.	26.	0.	7.	1.	16.	34.	0.	2.	0.	1.	0.	0.	2.7
22	K Ca Si	0.	1.	10.	17.	0.	9.	2.	31.	27.	1.	1.	0.	1.	0.	0.	2.1
20	Si Ca K	0.	0.	9.	36.	0.	6.	1.	19.	25.	2.	1.	0.	1.	0.	0.	2.3
16	Si K Ca	0.	0.	9.	42.	0.	4.	0.	27.	16.	1.	1.	0.	0.	0.	0.	1.6
12	K Si Ca	0.	0.	17.	25.	0.	4.	0.	33.	19.	1.	0.	0.	0.	0.	0.	1.1
47	Ca K S	0.	0.	6.	7.	0.	17.	1.	26.	38.	1.	2.	0.	1.	0.	0.	4.0
38	K Ca S	0.	0.	7.	9.	0.	18.	1.	36.	25.	1.	1.	0.	1.	0.	0.	3.2
21	K S Ca	0.	0.	8.	8.	0.	24.	1.	43.	18.	1.	1.	0.	1.	0.	0.	2.3
14	Ca S K	0.	0.	5.	9.	0.	23.	1.	18.	39.	1.	1.	0.	0.	0.	0.	1.2
4	Si Ca S	0.	0.	9.	30.	0.	21.	0.	11.	27.	1.	2.	0.	0.	0.	0.	0.6
10	Ca Al Fe	0.	3.	16.	6.	0.	0.	0.	0.	65.	0.	9.	0.	0.	0.	0.	0.8
7	Na K Ca	33.	0.	3.	4.	0.	9.	6.	25.	19.	2.	0.	0.	0.	0.	0.	1.2
10	Ca K Al	0.	0.	14.	10.	0.	8.	0.	27.	35.	3.	2.	0.	0.	0.	0.	1.0
8	Ca Si Mg	0.	10.	1.	15.	0.	0.	0.	1.	66.	3.	3.	0.	0.	0.	0.	0.7
33	OTHERS -	0.	5.	9.	18.	0.	3.	1.	8.	38.	7.	11.	0.	1.	0.	0.	2.3
139	ALL CATEGORIES WITH VOLUME % LESS THAN 1.0 COMBINED IN ONE																8.4

TABLE 4-77. - PSIT Beulah ash WITH ion exchange. 3s RST
(Coal #392) (Cont.)

1194 TOTALS - 1. 1. 16. 23. 0. 5. 1. 20. 28. 1. 4. 0. 0. 0. 0. 100.0

SAMPLE # 551 PSI Beulah ash WITH ion exchange, 3 sec. RST., (COAL # 392)

NUMBER 551 DISK 50 FILE 129 - 132 PARTICLES

RUN 1 DATE 25-JUN-91 SUMMARY 132 TOTAL 1199

BLOCKS 0 TIME 1045 OFF-PT. 32.00 >>500U 0

VOLUME DISTRIBUTION

SPECIES Volume % 0.0-2.5 2.5-5.0 5.0-10. 10.- 20. 20.- 40. 40.- 80. 80.-500.

K Si Al 14.7 25. 39. 13. 7. 8. 6. 2.
 Si Al K 4.0 18. 40. 10. 0. 8. 16. 8.

Ca Si Al 20.2 21. 42. 17. 8. 7. 3. 1.
 Ca Al Si 4.6 18. 32. 11. 34. 4. 0. 0.

OTHERS - 56.4 12. 21. 19. 22. 12. 13. 2.

TOTALS - 100.0 16. 29. 17. 16. 10. 9. 2.

TABLE 4-78. - Mössbauer results for UA "CUP + IM1" samples (Kentucky #11)

<u>Sample</u>	<u>IS</u>	<u>QS</u>	<u>H0</u>	<u>%Fe</u>	<u>Phase</u>
UKY 650	0.38	-0.08	513	18	Hematite
MK0958	0.31	-	487	24	Magnetite
56-6-CUP-A'	0.64	-	456	23	Magnetite
1240 C	0.62	-	414	9	Magnetite
	0.66	1.86	-	11	Fe/oxide??
	0.34	0.75	-	11	Fe/glass??
UKY 653	0.38	-0.09	513	8	Hematite
MK0957	0.30	-	488	26	Magnetite
56-6-CUP-D'	0.63	-	456	26	Magnetite
1430 C	0.64	-	414	10	Magnetite
	0.38	0.99	-	16	Fe ³⁺ /glass
	0.95	1.98	-	14	Fe ²⁺ /glass
UKY 656	0.40	-0.10	515	4	Hematite
MK1039	0.31	-	489	17	Magnetite
57-6-CUP-A'	0.69	-	456	34	Magnetite
1120 C, sub	0.76	-	303	3	Fe sulfide
	0.31	0.62	-	16	Pyrite?
	0.94	1.87	-	24	Fe ²⁺ /glass
UKY 659	0.38	-0.06	514	11	Hematite
MK0959	0.32	-	491	22	Magnetite
58-6-CUP-C'	0.59	-	460	19	Magnetite
1440 C, super	0.60	-	421	10	Magnetite
	0.36	1.26	-	27	Fe ³⁺ /glass
	1.07	2.12	-	12	Fe ²⁺ /glass

Mössbauer parameters are isomer shift (IS) relative to metallic iron and quadrupole splitting (QS) in mm/s; magnetic hyperfine splitting (H0) in kGauss; and percentage of iron in a given phase (%Fe).

TABLE 4-79. - Mössbauer data for ash samples from various coals

Sample	Hematite	Magnetite	Ferric glass	Ferrous glass	Other Phases
Im1 + Cup, UA 51B Ill #6 SOAP			23		77 (spm oxide)
Im1, UA 47B Ill #6 Coal	19	62	19		
Im1, UA 48B Beulah 48-1-im1B'		63	37		
Im1, UA 48F Beulah 48-1-im1-F1		62	38		
LY Test 4 SECV	20	43	37		
LY Test 3 (Trd.) SECV	25	24	51		
Beulah, Comb. Cham., SECV	21	50	24		
Beulah dep. cooled probe SECV	30	36	34		
Beulah dep. bank 1 SECV	69		31		
Beulah dep. bank 3 SECV	69		31		
Ill #6 coal 21-7-11-Im1-A		84	16		
Upper Freeport 35-03-11-Im1-A	6	54	26	14	
Upper Freeport 32-03-11-Im1-A	3	67	18	13	
Kentucky #11 27-06-11-Im1-E	8	67	12	14	
Beulah Lignite 22-01-11-Im1-A		71	24	5	
Eagle Bu. e 23-02-11-Im1-A		46	54		

Volume frequency for Beulah Lignite Coal (#592)

Figure 4-1. - Volume percentage - ternary composition diagram for Ca-Fe-S phases in Beulah coal.

Figure 4-2. Least squares analysis of the XANES from a Gravimelt-cleaned Kentucky #9 coal.

AIM

Association for Information and Image Management
1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

4 of 6

Figure 4-3. - Nepheline on filter.

#483 K-Si-Al vol. frequency for Nepheline

#483 Na-Si-Al vol. frequency for Nepheline

Figure 4-4. - Na-Si-Al volume frequency for Nepheline.

Figure 4-5. - Montmorillonite on filter.

#482 Ca + Fe + K-Si-Al vol. frequency for Montmorillonite

#482 K-Si-Al vol. frequency for Montmorillonite

#482 Ca-Si-Al vol. frequency for Montmorillonite

Figure 4-6. - Volume frequency for Montmorillonite.

Figure 4-7. - UA run 22 Beulah ash impactor #1.

#284 Ca-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #1.

Na-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #1.

#284 Fe-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #1.

K-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #1.

Figure 4-8. - Volume frequency for UA run 22 Beulah Lignite impactor #1.

#286 UA run 22 Beulah ash Imp #3

#286 UA run 22 Beulah ash Imp #3.

#286 UA run 23 Beulah ash Imp #3.

#286 UA run 22 Beulah ash Imp #3.

Figure 4-9. - UA runs 22 and 23 Beulah ash impactor #3.

#286 Ca-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #3.

Na-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #3.

#286 Fe-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #3.

36 K-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #3.

Figure 4-10. - Volume frequency for UA run 22 Beulah Lignite impactor #3.

#288 Ca-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #5.

#288 Na-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #5.

Figure 4-11. - Volume frequency for UA run 22 Beulah Lignite impactor #5.

#290 UA run 22 Beulah ash Imp #7

#290 Ca-Na-S vol. frequency for UA run 22 Beulah Lignite Imp #7.

#290 Na-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #7.

Ca-Si-Al vol. frequency for UA run 22 Beulah Lignite Imp #7.

FIGURE 4-12. - Volume frequency for UA run 22 Beulah Lignite impactor #7.

Figure 4-13. - Volume frequency for PSIT Beulah Lignite ash 7% oxygen, 1500 K.

FIGURE 4-14. - Volume frequency for PSIT Beulah Lignite ash 21% oxygen, 1500 K.

FIGURE 4-15. - UA run 23 Eagle Butte impactor #1.

Ca
#293 Ca-Si-Al vol. frequency for UA run 23 Eagle Butte
Imp #1.

K
#293 K-Si-Al vol. frequency for UA run 23 Eagle Butte
Imp #1.

Fe
Fe-Si-Al vol. frequency for UA run 23 Eagle Butte
Imp #1.

FIGURE 4-16. - Volume frequency for UA run 23 Eagle Butte impactor #1.

#297 UA run 23 Eagle Butte Imp 5

#297 Ca-Si-Al vol. frequency for UA run 23 Eagle Butte
Imp #5

FIGURE 4-17. - UA run 23 Eagle Butte impactor #5.

Ca-Si-Al vol. frequency for PSI/MIT-2 DTF run on Eagle Butte, 1750K, 7% oxygen

Ca-Al-Mg vol. frequency for PSI/MIT-2 DTF run on Eagle Butte, 1750K, 7% oxygen

FIGURE 4-18. - Ca-Al-Mg volume frequency for PSIT/MIT-2 DTF run on Eagle Butte, 1750 K, 7% oxygen.

#243 PSI ID #1g-a KY#9, 7% O₂, 2350F

#245 PSI ID #1i, Ky #9, 21% O₂, 2350F

FIGURE 4-19. - PSIT ID #1g-a Kentucky #9, 7% O₂, 2350F.

#245 K-Si-Al vol. frequency for PSI #1i KY #9,
0.2 g/min, 21% O₂, 2350F.

#245 Fe-Si-Al vol. frequency for PSI #1i KY #9,
0.2 g/min, 21% O₂, 2350F.

#243 K-Si-Al vol. frequency for PSI #1g-a KY #9,
0.2 g/min, 7% O₂, 2350F.

#243 Fe-Si-Al vol. frequency for PSI #1g-a KY #9,
0.2 g/min, 7% O₂, 2350F.

FIGURE 4-20. - K-Si-Al volume frequency for PSIT #1g-a Kentucky #9, 0.2 g/min,
7% O₂, 2350F.

FIGURE 4-21. - UA run 24 Kentucky #9 impactor #1.

FIGURE 4-22. - Volume frequency for UA run 24 Kentucky #9 impactor #1.

FIGURE 4-23. - PSIT Kentucky #11 ash, 7% O₂, 1500 K.

FIGURE 4-24. - Volume frequency for PSIT Kentucky #11 ash, 7% oxygen, 1500 K.

FIGURE 4-25. - Volume frequency for UA run 27 Kentucky #11 impactor #1.

Fe

Al

Al

K

#117 vol. frequency for UA run 32 Upper Freeport
Imp #1.

Fe

#119 vol. frequency for UA run 32 Upper
Freeport Imp #3.

FIGURE 4-26. - Volume frequency for UA run 32 Upper Freeport.

#246 PSI ID #if, Ill #6, 7% O₂, 2350F

FIGURE 4-27. - PSIT ID #if, Illinois #6, 7% O₂, 1500 K.

#246 vol. frequency for PSI #if III #6,
0.2 g/min, 7% O₂, 2350F.

FIGURE 4-28. - Volume frequency for PSIT #if Illinois #6, 0.2 g/min, 7% O₂, 1500 K.

#275 UA run 21 Illinois #6 Imp #1

FIGURE 4-29. - UA run 21 Illinois #6 impactor #1.

#275 vol. frequency for UA run 21 Illinois #6
Imp #1.

FIGURE 4-30. - Volume frequency for UA run 21 Illinois #6 impactor #1.

PSI San Miguel Lignite ash 7% O₂, 2350F, 3 sec. RST

vol. frequency for PSI San Miguel lignite ash
7% oxygen, 2350 F, 3 sec RST.

**FIGURE 4-31. - Volume frequency for PSIT San Miguel lignite ash, 7% oxygen,
1500 K, 3s RST.**

PSI San Miguel Lignite ash 21% O_2 , 2350F, 3 sec RST

vol. frequency for PSI San Miguel lignite ash
21% oxygen, 2350 F, 3 sec RST.

Figure 4-32. - Volume frequency for PSIT San Miguel lignite ash, 21% oxygen,
1500 K, 3s RST.

FIGURE 4-33. - UA run 47B, Illinois #6, impactor #1 + cup.

FIGURE 4-34. - Volume frequency for UA run 47B, Illinois #6 Impactors 1 + cup.

FIGURE 4-35. - UA run 47B, Illinois #6, impactors 2 + 3 + 4.

FIGURE 4-36. - Volume frequency for UA run 47B, Illinois #6 impactors 2+3+4.

FIGURE 4-37. - UA run 47B, Illinois #6, impactors 5+6+7+8+AF.

**FIGURE 4-38. - Volume frequency for UA run 47B,
Illinois #6 impactors 5+6+7+8+AF.**

#553 UA run 47B, Ill #6, Imp 2+3+4

#553 S-Si-Al vol. frequency for UA run 47B, Illinois #6
Impactors 2+3+4

#555 UA run 47D, Illinois #6, Imp 1+cup

#556 S-Si-Al vol. frequency for UA run 47D, Illinois #6
Impactors 2+3+4.

FIGURE 4-39. - Volume frequency for UA run 47B, Illinois #6, impactors 2+3+4.

FIGURE 4-40. - UA run 51B, Illinois #6 SOAP, impactors 1+cup.

FIGURE 4-41. - Volume frequency for UA run 51B Illinois #6 SOAP impactors 1+cup.

FIGURE 4-42. - UA run 51B, Illinois #6 SOAP, impactors 2+3+4.

#584 UA run 51B, Illinois #6 SOAP, Imp 5+6+7+8+AF

#584 Fe-Si-Al vol. frequency for UA run 51B Illinois #6
SOAP Impactors 5+6+7+8+AF.

FIGURE 4-43. - UA run 51B, Illinois #6 SOAP, impactors 5+6+7+8+AF.

FIGURE 4-44. - UA run 48F, Beulah lignite, impactors 1+cup.

FIGURE 4-45. - UA run 48D, Beulah lignite, impactors 2+3+4.

#565 UA run 48B, Beulah lignite Imp 2+3+4

#565 Ca-S-Na vol. frequency for UA run 48B, Beulah lignite Impactors 2-3+4.

FIGURE 4-46. - UA run 48B, Beulah lignite impactors 2+3+4.

FIGURE 4-47. - UA run 48B, Beulah lignite, impactors 5+6+7+8+AF.

FIGURE 4-48. - Volume frequency for UA run 48B, Beulah lignite impactors 5+6+7+8+AF.

#596 SECV Beulah lignite ash probe (combustion chamber)

#596 Ca-Si-Al vol. frequency for SECV Beulah lignite ash probe (combustion chamber)

#596 SECV Beulah lignite ash probe (combustion chamber)

#596 Na-Si-Al vol. frequency for SECV Beulah lignite ash probe (combustion chamber).

FIGURE 4-49. - Volume frequency for PSIT/SECV Beulah lignite ash probe (combustion chamber).

#597 SECV Beulah lignite ash probe (horizontal duct)

#597 Ca-Si-Al vol. frequency for SECV Beulah lignite ash probe (horizontal duct)

#597 SECV Beulah lignite ash probe (horizontal duct)

#597 Na-Si-Al vol. frequency for SECV Beulah lignite ash probe (horizontal duct)

FIGURE 4-50. - Volume frequency for PSIT/SECV Beulah lignite ash probe (horizontal duct).

#601 SECV Beulah lignite precipitator ash

#601 Na-Si-Al vol. frequency for SECV Beulah lignite precipitator ash

#601 SECV Beulah lignite precipitator ash

#601 Na-S-Ca vol. frequency for SECV Beulah lignite precipitator ash

FIGURE 4-51. - Volume frequency for PSIT/SECV Beulah lignite precipitator ash.

FIGURE 4-52. - PSIT/SECV Beulah lignite ash probe (combustion chamber).

FIGURE 4-53. - UA runs 49B and 49H, Loy Yang 2301, impactors 5+6+7+8+AF.

3 Ca-S-Mg vol. frequency for UA run 49B Loy Yang 2301 Imp 1 + cup. #574 Ca-S-Mg vol. frequency for UA run 49B Loy Yang 2301 Imp 2+3+4.

6 Ca-S-Mg vol. frequency for UA run 49H Loy Yang 2301 Imp 1 + cup. #577 Ca-S-Mg vol. frequency for UA run 49H Loy Yang 2301 Imp 2+3+4.

FIGURE 4-54. - Volume frequency for UA runs 49B and 49H Loy Yang 2301.

#573 UA run 49B, Loy Yang 2301, Imp 1 + cup

#574 UA run 49B, Loy Yang 2301, Imp 2+3+4

#575 UA run 49B, Loy Yang 2301, Imp 5+6+7+8+AF

FIGURE 4-55. - UA run 49B, Loy Yang 2301.

#573 Ca-S-Cl vol. frequency for UA run 49B Loy Yang 2301
Imp 1 + cup.

#575 Na-S-Cl vol. frequency for UA run 49B Loy Yang 2301
Imp 5+6+7+8+AF.

FIGURE 4-56. - Volume frequency for UA run 49B, Loy Yang 2301.

#578 Ua run 49H, Loy Yang 2301, Imp 5+6+7+8+AF

#578 Mg-Cl-S vol. frequency for UA run 49H Loy Yang 2301
Imp 5+6+7+8+AF.

**FIGURE 5-57. - Volume frequency for UA run 49H Loy Yang 2301,
impactors 5+6+7+8+AF.**

FIGURE 5-58. - Loy Yang 2301.

#577 UA run 49H, Loy Yang 2301, Imp 2+3+4

#577 Ca-Fe-Mg vol. frequency for UA run 49H Loy Yang 2301
1Imp 2+3+4.

FIGURE 4-59. - Volume frequency for UA run 49H, Loy Yang 2301, impactors 2+3+4.

#580 UA run 50D, Loy Yang 1953, Imp 2+3+4

#580 UA run 50D, Loy Yang 1953, Imp 2+3+4

#580 UA run 50D, Loy Yang 1953, Imp 2+3+4

FIGURE 4-60. - UA run 50D, Loy Yang 1953, impactors 2+3+4.

#581 UA run 50D, Loy Yang 1953, Imp 5+6+7+8+AF

#581 UA run 50D, Loy Yang 1953, Imp 5+6+7+8+AF

#581 UA run 50D, Loy Yang, 1953, Imp 5+6+7+8+AF

#581 UA run 50D, Loy Yang 1953, Imp 5+6+7+8+AF

FIGURE 4-61. - UA run 50D, Loy Yang 1953, impactors 5+6+7+8+AF.

#581 Ca-S-K vol. frequency for UA run 50D Loy Yang 1953
Imp 5+6+7+8+AF.

#581 Na-S-K vol. frequency for UA run 50D Loy Yang 1953
Imp 5+6+7+8+AF.

**FIGURE 4-62. - Volume frequency for UA run 50D, Loy Yang 1953,
impactors 5+6+7+8+AF.**

#593 SECV Loy Yang Test #1, ash probe (ring 7), Untreated

Mg-Ca-Al vol. frequency for SECV test #1 on untreated Loy Yang ash probe (ring 7).

FIGURE 4-63. - Volume frequency for PSIT/SECV test #1.

#594 SECV Loy Yang Test #4, ash probe (horizontal duct), Untreated #599 SECV Loy Yang Test #4, precipitator ash, Untreated

#595 SECV Loy Yang Test #3, ash probe (horizontal duct), Treated #600 SECV Loy Yang Test #3, precipitator ash, Treated

FIGURE 4-64. - PSIT/SECV Loy Yang test #4, Mg-Al-Ca.

#593 SECV Loy Yang Test #1, ash probe (ring 7), Untreated

#594 SECV Loy Yang Test #4, ash probe (horizontal duct), Untreated

#598 SECV Loy Yang Test #1, precipitator ash, Untreated

FIGURE 4-65. - PSIT/SECV Loy Yang, Fe-Mg-Al.

#598 SECV Loy Yang 1953 Test #1, precipitator ash, Untreated

#599 SECV Loy Yang Test #4, precipitator ash, Untreated

FIGURE 4-66. - PSIT/SECV Loy Yang 1953, Na-S-Cl.

#593 Na-Si-Al vol. frequency for SECV test #1 on untreated Loy Yang ash probe (ring 7).

#594 Na-Si-Al Col. frequency for SECV Test #4 on untreated Loy Yang ash probe (horizontal duct)

FIGURE 4-67. - Na-Si-Al volume frequency for PSIT/SECV test #1 on untreated Loy Yang ash probe (ring 7) and Na-Si-Al col. frequency for PSIT/SECV test #4 on untreated Loy Yang ash probe (horizontal duct).

#548 beulah ash w/o ion exchange 1 sec. RST. (coal #392)

#551 Beulah ash with ion exchange, 3 sec. RST

#550 Beulah ash with ion exchange, 1 sec. RST

FIGURE 4-68. - Ion-exchanged Beulah coal: Ca-Al-Si ash.

vol. frequency for Beulah ash w/o ion exchange
1 sec. RST.

vol. frequency for Beulah ash w/o ion exchange
3 sec. RST.

vol. frequency for Beulah ash with ion exchange
1 sec. RST.

vol. frequency for Beulah ash with ion exchange
3 sec. RST.

FIGURE 4-69. - Volume frequency for ion-exchanged Beulah ash.

#548 beulah ash w/o ion exchange 1 sec. RST (coal #392)

#549 Beulah ash

#550 Beulah ash with ion exchange, 1 sec. RST

#551 Beulah ash with ion exchange, 3 sec. RST

FIGURE 4-70. - K-Al-Si Beulah ash (ion-exchanged sample).

vol. frequency for Beulah ash w/o ion exchange
1 sec. RST.

vol. frequency for Beulah ash w/o ion exchange
3 sec. RST.

vol. frequency for Beulah ash with ion exchange
1 sec. RST.

vol. frequency for Beulah ash with ion exchange
3 sec. RST.

FIGURE 4-71. - Volume frequency for Beulah ash, ion-exchanged sample.

#550 Beulah ash with ion exchange, 1 sec. RST

vol. frequency for Beulah ash with ion exchange
1 sec. RST.

#550 Beulah ash with ion exchange, 1 sec. RST

vol. frequency for Beulah ash with ion exchange
1 sec. RST.

FIGURE 4-72. - Volume frequency for Beulah ash, ion-exchanged sample.

#551 Beulah ash with ion exchange, 3 sec. RST

Ca-S-K vol. frequency for Beulah ash with ion exchange
3 sec. RST.

FIGURE 4-73. - Volume frequency for Beulah ash, ion-exchanged sample.

CPFLS / UNIVERSITY OF KENTUCKY

TUE 05-JUN-92 08:16

Cursor: 0.000keV = 0

ROI

(0) 0.000: 0.000

FIGURE 4-74. - Energy dispersive X-ray (EDX) spectrum of the ceramic tube, PSIT/SECV tests.

FIGURE 4-75. - SEM micrograph for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606).

FIGURE 4-76. - SEM X-ray maps for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606).

FIGURE 4-77. - SEM micrograph for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606).

FIGURE 4-78. - SEM X-ray maps for PSIT/SECV test #1 long-term deposits, Loy Yang (untreated) (CFFLS #606).

FIGURE 4-79. - SEM micrograph for PSIT/SECV test #1 long-term deposits,
Loy Yang (untreated) (CFFLS #606).

FIGURE 4-80. - SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607).

FIGURE 4-81. - SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607).

FIGURE 4-82. - SEM micrograph for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607).

FIGURE 4-83. - SEM X-ray maps for PSIT/SECV test #4 short-term deposits, Loy Yang (untreated) (CFFLS #607).

FIGURE 4-84. - SEM micrograph for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608).

FIGURE 4-85. - SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608).

FIGURE 4-86. - SEM micrograph for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608).

FIGURE 4-87. - SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608).

FIGURE 4-88. - Energy Dispersive X-ray (EDX) spectrum of region 1 in Figure 4-86.

FIGURE 4-89. - SEM X-ray maps for PSIT/SECV test #4 long-term deposits, Loy Yang (untreated) (CFFLS #608).

FIGURE 4-90. - SEM micrograph for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609).

FIGURE 4-91. - SEM X-ray maps for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609).

FIGURE 4-92. - SEM micrograph for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609).

FIGURE 4-93. - SEM X-ray maps for PSIT/SECV short-term deposits of Beulah lignite (CFFLS #609).

FIGURE 4-94. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-95. - SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-96. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-97. - SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-98. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-99. - SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-100. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-101. - Energy dispersive X-ray (EDX) spectra of different regions marked in Figure 4-100.

FIGURE 4-102. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-103. - SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-104. - SEM micrograph for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-105. - SEM X-ray maps for PSIT/SECV long-term deposits of Beulah lignite (CFFLS #610).

FIGURE 4-106. - Mössbauer spectra obtained from ash probe samples taken during PSIT/SECV tests.

FIGURE 4-107. - XANES for Ca standard compounds.

FIGURE 4-108. - EXAFS RSF for Ca standard compounds.

FIGURE 109. - EXAFS RSF for Ca standard compounds.

FIGURE 4-110. - XANES of calcium acetate treated sucrose char (top) and of samples prepared from it in a DTF.

FIGURE 4-111. - Ca RSF derived from EXAFS of sucrose chars with Ca $(\text{CH}_3\text{CO})_2$ and SiO_2 formed in MIT drop tube furnace at wall temperature with 20% oxygen partial pressure.

Association for Information and Image Management
1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

5 of 6

FIGURE 4-112. - Ca XANES from suite of model chars prepared by MIT group.

FIGURE 4-113. - RSF of two model ashes from MIT.

FIGURE 4-114. - Typical Ca XANES for impactor 1 and higher impactor number ash samples.

FIGURE 4-115. - RSF of the Beulah and Eagle Butte impactor 1 as samples.

FIGURE 4-116. - Ca XANES for ash from Beulah parent and ion exchanged coal.

FIGURE 4-117. - XANES of potassium standard compounds.

FIGURE 4-118. - Comparison of the XANES of K_2SO_4 to that of the ion-exchanged ash samples and an MIT sample.

FIGURE 4-119. - RSF of K_2SO_4 compared to that of an ion-exchanged ash and an MIT sample.

FIGURE 4-120. - Potassium XANES spectra of a series of MIT samples.

FIGURE 4-121. - In-situ K-XANES of KOH-Kaolinite mixture at different temperatures.

FIGURE 4-122. - Ca XANES of in-situ reaction between Ca (OH)₂ and kaolinite.

FIGURE 4-123. - High temperature in-situ Fe XANES of ash.

FIGURE 4-124. - Radial structure function of high temperature in-situ Fe EXAFS.

FIGURE 4-125. - As K-edge XANES spectra of Upper Freeport coal fractions and ash.

SECTION 5

TASK 5

FUNDAMENTAL STUDIES OF MINERAL MATTER VAPORIZATION AND RESIDUAL ASH FORMATION (MIT)

5. FUNDAMENTAL STUDIES OF MINERAL MATTER VAPORIZATION AND RESIDUAL ASH FORMATION (MIT)

5.1 Background

The study of mineral matter transformations during combustion is motivated by concerns with slagging and fouling and with the vaporization of selected inorganic constituents in the coal during combustion, leading to the formation of a fine aerosol of potential environmental concern. These problems are very closely related to the size and composition distributions of fly ash particles generated in the furnace.

Studies show that the size distribution of the fly ash particles is bimodal (McElroy et al., 1982). The submicron mode is centered about a volume mean diameter of $0.1\ \mu\text{m}$ and is formed from the vaporization and condensation of inorganic species. The vapors of the more volatile metals and the fume can contribute to fouling of heat exchange surfaces. The vapors can condense on particles or heat exchange surfaces forming a sticky layer and the fume can deposit via thermophoresis. Also, submicron ash particles are difficult to remove from the gas stream, effectively penetrate into the deep lung (Nat. Air Pollution Control Board, 1969), are enriched in toxic trace species (Pb, Zn, As, etc.) (Davidson et al., 1974; Haynes et al., 1982), and are often coated with a layer of H_2SO_4 (Lewis, 1987). A toxicological study (Amdur et al., 1986) has shown that submicron ash, especially when coated with H_2SO_4 , is a serious respiratory irritant.

The larger, residual ash mode is made up of particles 1 to $50\ \mu\text{m}$ in diameter which remain after the carbon matrix burns away. Although the residual ash particles are captured with 98 to 99+ % efficiency and do not cause any significant air pollution problems, they cause boiler operational problems such as inefficient heat transfer and intermittent boiler shutdown. The residual ash particle size distribution varies widely depending on the coal. The size and composition of the residual ash determine the probability that it will impact and stick to heat exchange surfaces.

Fundamental understanding of mineral matter transformations is necessary in order to mitigate the above-mentioned problems caused by fly ash particles of different sizes and compositions. A good portion of MIT's experimental and theoretical studies had been carried out and reported in Phase I of this program. Efforts on a better understanding of the mineral matter transformation were further exerted in Phase II, with emphasis on the effects of coal beneficiation on ash formation.

This section reports additional experimental and theoretical work carried out at MIT during Phase II of this program. Subsection 5.2 describes the experimental apparatus used for the vaporization and residual ash formation studies. Subsection 5.3 reports the vaporization study results. In Subsection 5.3.1, the combustion modeling work carried out to interpret the experimental data on vaporization is presented. In Subsection 5.3.2, the vaporization results, their interpretation and the modeling work are presented. Subsection 5.4 reports the work related to residual ash formation. In Subsection 5.4.1, the

performance of the clean coals in a laminar flow reactor is discussed. Subsection 5.4.2 presents the completed work on the effect of char structure on ash formation. Subsection 5.4.3 presents the results of synthetic char experiments to study the effect of alkali species on ash coalescence. Subsection 5.4.4 presents additional modeling work on residual ash formation. Finally, Subsection 5.5 concludes the work of MIT during the Phase II of the program.

5.2 Experimental Apparatus

5.2.1 Laminar, Entrained-Flow Reactor

Combustion experiments were performed with a laminar, entrained-flow reactor which was designed to expose a single stream of particles to a high temperature environment with an independently variable feedrate, gas temperature, gas composition, and residence time.

As shown in Figure 5.2-1, the laminar, entrained-flow reactor was a vertically oriented, externally heated alumina tube containing gas in downward laminar flow. The heat was provided by an Astro Model 1000A-3560 graphite element furnace. The heated section was 430 mm long. The first 170 mm served as a preheat section upstream of the particle injection. The last 50 mm of the preheat section (i.e., between 120 and 170 mm) was filled with an alumina honeycomb to act as a flow straightener in order to ensure laminar flow. Six thousand std ml/min of main gas entered through this preheat section.

The water-cooled injection probe passed through the center of the preheat section and was flush with the bottom of the honeycomb. Particles were injected concurrently into the center of the preheated main gas flow with approximately 80 std ml/min of entrainment N_2 at room temperature. The heated reaction zone following particle injection was 50 mm in diameter and 260 mm in length.

The sample feeding was done by entrainment of size-classified sample particles with N_2 . The particles were contained in a test tube pressurized with N_2 . A hypodermic stainless steel tube with a 0.8 mm I.D. was inserted over the bed. As approximately 70 std ml/min of N_2 passed over the bed and into the hypodermic, particles were entrained. The hypodermic was maintained near the surface of the particle bed by continuously pushing the test tube towards the hypodermic. This was accomplished by mounting the apparatus on a syringe pump. The particle feedrate was controlled by changing the speed of the syringe pump. The other end of the hypodermic was inserted into the open 3.2 mm (1/8 in.) I.D. core of the water-cooled injection probe. The tip of the hypodermic was maintained 5 cm (2 in.) above the end of the injection probe.

After injection the particles were entrained in the main gas and passed through the heated reaction zone. The reaction zone was designed to operate between 1000 and 1750 K. The maximum residence times at these temperatures, assuming fully developed laminar velocity profiles (particles were injected on the reactor centerline where the gas velocity was twice the mean velocity) with 6 slpm of main gas, were 0.77 and 0.44s, respectively.

FIGURE 5.2-1. - MIT laminar entrained flow reactor.

After passing through the reaction zone the entire gas stream was pulled through the water-cooled collection probe. The reactor was designed so that the collection probe could be inserted to any position within the heated reaction zone, thus allowing for control of the residence time. In order to rapidly quench the reaction products, 10 to 20 slpm of room temperature N_2 were added to the 6 slpm of main gas within the first 20 mm of the collection probe. This was accomplished by constructing the inner wall of the collection probe from porous sintered stainless steel through which N_2 was transpired. The amount of quench gas to be added was varied depending on the outlet temperature desired. In order to prevent deposition on the inside walls of the collection probe after the quench section, an additional 4 slpm was radially transpired through the remaining 690 mm of the sintered stainless tube. This brought the total volumetric flow of gas exiting the collection probe to between 20 and 30 slpm. The exit gas and particles were then pulled through an aerosol collection/classification device and vacuum pump which is the subject of Subection 5.2.3.

The entrainment system restricted the operating condition. Dry size-classified particle samples between 40 and 150 μm (typical size cuts: 63 to 75 μm , 90 to 105 μm) were fed successfully. However, moisture and fines caused agglomeration. Agglomeration and oversize particles caused plugging in the hypodermic tubing. Feedrates of 0.002 to 0.02 g/min were easily achieved with char samples. Feedrates greater than 0.02 g/min often plugged the hypodermic tubing. Thus, most experiments were run with feedrates of 0.01 to 0.02 g/min.

The centerline gas temperature was measured as a function of axial furnace location under normal operating conditions using a 1.6 mm (1/16 in.) O.D. molybdenum sheathed tungsten-rhenium thermocouple. Considerable error due to heat conduction along the thermocouple was introduced when steep gradients in temperature were measured. In order to bracket the uncertainty, the temperature measurements were made with the thermocouple inserted through both the injection and collection probes. The temperature profiles are shown in Figure 5.2-2 with the uncertainty represented by the shaded areas. Note that both the furnace setting and the position of the collection probe impact the temperature profile.

The I.D. of the collection probe was one-half of an inch; consequently, the entrance to the probe from the reaction zone was an abrupt contraction and any large particles further than one-quarter of an inch from the reactor centerline could have been inertially separated and would have remained in the furnace. Care was taken to routinely align the injection probe so as to place the particles near the reactor centerline.

Previous researchers (Neville, 1982; Quann, 1982) tested the collection efficiency under normal operating conditions and reported that when the injection probe was aligned correctly, over 90% of most elemental species fed to the furnace were recovered.

Additional information is provided in Graham (1991) and Kang (1991).

5.2.2 Pyrolysis Furnace

For the preparation of well-defined synthetic chars, a pyrolysis furnace was built which can provide a high temperature, inert environment. A cross-section of the furnace is shown in Figure 5.2-3. The resistance heater shown in Figure 5.2-3 was a 220V, 1850W Lindberg furnace with a cylindrical hot zone 51 cm (20 in.) in length and 11.4 cm (4.5 in.) in diameter. The quartz reaction tube was 91.4 cm (36 in.) long and 7.3 cm (2-7/8 in.) in diameter. The reaction tube was held in the furnace by cylindrical insulation inserts. Access was provided to the reaction tube via a ground glass joint on the downstream side. The ground glass joint was placed far enough away from the hot zone to make a greased, gas-tight seal possible. Both ends of the reaction tube were drawn down to 6.4 mm (1/4 in.) O.D. to facilitate gas injection and withdrawal. A type R thermocouple was inserted into the furnace through the gas inlet on the upstream side to monitor furnace temperature. A disposable fiberglass filter was placed just downstream of the hot zone to capture condensing tars. The gases exiting the reaction tube passed through a water condensation trap and a bubble column. The bubble column was used to control the pressure in the furnace.

FIGURE 5.2-2. - Temperature profiles in the MIT laminar entrained flow reactor.

The samples were placed in the furnace in 20.3 cm (8 in.) long alumina boats. The alumina boats were made from 5.7 cm (2-1/4 in.) O.D. alumina tubes and 5.1 cm (2 in.) alumina disks which were split and glued together with ceramic cement.

The furnace was operated at approximately 10 cm H₂O pressure and approximately 0.4 std l/min of O₂ free N₂ (i.e., <5 ppm O₂) purge gas. The positive pressure prevented air leaks into the furnace and the purge gas turned over the reactor volume every 5 min to facilitate removal of the pyrolysis products.

The furnace was operated at temperatures from 500 to 1100 K. Temperature profiles for 550 and 880 K are shown in Figure 5.2-4. The 20.3 cm hot zone indicates the position of the alumina boats during operation.

The procedure for generating synthetic chars using this furnace is described in a later section (Subsection 5.3.2.1.2). Additional information is provided in Graham (1991).

C-1684

FIGURE 5.2-3. - Pyrolysis furnace used for synthetic char preparation.

5.2.3 Aerosol Collection Equipment

One or more of the following three devices - absolute filter, cascade impactor, and electrostatic precipitator - were used to collect and/or characterize the combustion aerosol as it exited the collection probe. Figure 5.2-5 illustrates the different collection systems and the information that was attainable using them. The absolute filter, cascade impactor, and the electrostatic precipitator will be discussed in the following three subsections.

5.2.3.1 Absolute Filter

The simplest aerosol collection system shown in Figure 5.2-5 is an absolute filter which was designed to separate all particulate matter from the gas stream. Three different Millipore membrane filters were used and the characteristics of each are shown in Table 5.2-1. The teflon/polyethylene filter was the most durable and was truly an absolute filter. When high temperature collection was required the teflon filter was used. The flourine in the teflon in either of the above mentioned filters interfered with elemental analysis for silicon. Therefore, when silicon analysis was required, the cellulose acetate/nitrate filter was used.

FIGURE 5.2-4. - Temperature profiles in the pyrolysis furnace.

5.2.3.2 Cascade Impactor

A cascade impactor was used to obtain ash particle size distributions. The cascade impactor was also used to remove the residual, supermicron ash and to capture the remaining submicron ash (see Figure 5.2-6) for submicron ash studies.

As shown in Figure 5.2-6, a cascade impactor consists of a series of stages, each composed of an orifice, or set of orifices, through which the aerosol flows and a collection surface normal to the flow immediately after the orifices upon which the aerosol impinges. Those particles with too much inertia cannot follow the gas streamlines, and hence impact on the collection surface and are separated from the gas stream. The process is repeated with several consecutive stages, with each subsequent stage removing smaller particles.

The cascade impactor used was a Mark II Model 20-800 non-viable ambient particle sizing sampler manufactured by Andersen 2000 Inc. The manufacturer's collection efficiency curves for each of the eight impactor stages and the preseparator are shown in Figure 5.2-7 for 30 l/min. Using preweighed aluminum foil substrates which were covered with a silicone spray grease (to prevent particle bounce and re-entrainment) and dried at 110°C, fly ash particle size distributions were determined from the combustion of a variety of coals in the laminar, entrained-flow reactor under a range of operating conditions. A modified Twomey algorithm and the above efficiency curves were used to invert the cascade impactor data and produce continuous fly ash particle size distributions. (For the details, see Appendix A.)

FIGURE 5.2-5. - Aerosol collection systems.

The purpose of the cascade impactor in this work was (1) to collect and size classify fly ash particles, and (2) to remove the residual, supermicron ash in order to isolate the submicron ash for subsequent collection and characterization. Using the impactor collection efficiency curves in Figure 5.2-7, the impactor configuration was optimized to remove particles greater than 1 μm. This was accomplished by operating the impactor with the preseparator and only the first six stages. The cumulative penetration curve for this configuration is given in Figure 5.2-8 for the different furnace operating conditions. These penetration curve are based on aerodynamic diameter which is the diameter of a sphere with a specific gravity of one with the same Stokes number as the particle. The Stokes number is proportional to density x (diameter)²; therefore, a sphere of specific gravity 3 will have an

TABLE 5.2-1. - Filter characteristics

Filter Material	Maximum Operating Temperature (°C)	Pore Size (μm)	Collection Efficiency			
			0.035 μm Particles	0.10 μm Particles	0.30 μm Particles	1.0 μm Particles
Cellulose Acetate/ Nitrate	121	0.20	> 99.999	> 99.999	> 99.999	> 99.999
Teflon/ Polyethylene	130	0.20	> 99.99	> 99.99	> 99.99	> 99.99
Teflon	260	5.0	95.1	99.8	99.98	> 99.99

(Collection efficiency data from Liu et al., 1983).

FIGURE 5.2-6. - Cascade impactor (after Friedlander, 1977).

FIGURE 5.2-7. - Removal efficiency versus particle size for each stage of the cascade impactor.

FIGURE 5.2-8. - Cumulative penetration curve for first six impactor stages.

aerodynamic diameter $\sqrt{3} = 1.73$ times its actual diameter. The 50% cutoff for the two operating conditions was 1 and 1.2 μm , aerodynamic diameter.

One should note that Figure 5.2-8 is a rigorous definition of what is collected as submicron ash in the first part of this work. Thus, it contains the implicit assumption that the material defined by Figure 5.2-8 contains all the submicron ash and nothing else.

5.3 Vaporization

5.3.1 Combustion Modeling

In order to interpret the vaporization data reported in the following section, char combustion temperatures and burning times were required. An effort was made at the beginning of this work (Phase I) to use two-color pyrometry to measure char temperatures and burning times. Unfortunately, the two-color pyrometry effort failed, and redesign of the pyrometer was outside the scope of this work. Consequently, char temperatures and burning times were calculated.

5.3.1.1 Previous Models

In order to develop the most accurate char combustion model possible, previous modeling efforts were first reviewed.

Basic Assumptions

During the past 65 years, char burnout during pulverized coal combustion has been modeled by a number of researchers such as Nusselt (1924), Spalding (1953), Field et al. (1967), Ayling and Smith (1972), Timothy et al. (1982), and Waters et al. (1988). Each of these researchers has made a similar set of readily justifiable assumptions in relation to the following set of basic questions:

- Can the energy and mass transport be modeled as a continuum?
- Do the particles influence one another?
- Is convection important?
- Is the particle isothermal?
- What chemical reactions must be considered?

Each of these assumptions will be discussed briefly with respect to the experiments performed in this work.

Can the energy and mass transport be modeled as a continuum?

A simple calculation shows that the mean free path of the gas is never significantly greater than 1 μm under the experimental conditions explored in this work. Thus, as long as the char particle is 10 μm or greater, the transport can be modeled as a continuum.

Do the particles influence one another?

In the laminar, entrained-flow reactor described earlier, each coal particle was injected along the same path down the centerline of the reactor at approximately 60 cm/s. At the maximum feedrate used (0.02 g/min) the particles were spaced over 10 diameters apart. Given the boundary layer surrounding the particles is generally considered to be 1 to 2 diameters, the particles were assumed to have no influence on one another.

Is convection important?

The maximum settling velocity, and hence the maximum velocity of the particles relative to the gas, for the experimental conditions of this work was always less than 40 cm/s. Using that velocity, the Sherwood and Nusselt numbers for a 100 μm sphere in air at 1650 K are virtually 2 (Satterfield, 1981); therefore, forced convection may be ignored and the char particles may be assumed to be suspended in a stagnant gas of infinite extent.

Is the particle isothermal?

If the characteristic time for conduction is defined as the energy transferred to the char particle/initial heating rate, then the characteristic conduction time for a 100 μm char particle is approximately 0.001s. The burn time for a 100 μm char particle is known to be between 1 and 0.1s. Thus, the particle can be assumed to be isothermal, and char combustion can be modeled assuming the char achieves a steady state temperature much more rapidly than the diameter changes. This conclusion was verified experimentally by Timothy et al. (1982), who, using two-color pyrometry to monitor the temperature history of burning char particles, showed that the temperature of the char was nearly constant during most of the burnout.

What chemical reactions must be considered?

As summarized by Field et al. (1967), there are a large number of possible reactions at the char surface and in the boundary layer. On the basis of known chemical kinetics and estimates of the relative concentrations of different chemical species, the significant reactions may be narrowed to the following three:

Thus, we are left with the same basic set of assumptions that most previous researchers have made in order to model char burnout. The char particles are assumed to burn independent of one another in a stagnant continuum of infinite extent. Combustion is assumed to be a pseudo steady-state process which involves no other reactions than 5.1, 5.2, and 5.3.

Controversial Assumptions

In order to complete their models, previous researchers have had to make further assumptions which have not been as easily justified. Typically such assumptions have included the following: reactions 5.2 and 5.3 may be ignored, the intrinsic reaction kinetics are fast enough that the combustion rate is limited entirely by bulk mass transfer, and O_2 dissociation in the char boundary layer may be ignored. Each of these assumptions will be reviewed in detail.

Reactions 5.2 and 5.3 may be ignored.

The extent to which the carbon is oxidized and where the oxidation occurs is directly related to the heat generation rate and, thus, the particle temperature. Consequently, this issue has received considerable attention over the years.

Several studies (Arthur, 1951; Rossberg, 1956; and Otterbein and Bonnetain, 1968) on the heterogeneous carbon oxidation product have experimentally shown that the CO/CO_2 ratio increases with temperature up to 1700 K. If these results are extrapolated to temperatures in excess of 2000 K, little CO_2 is expected as a heterogeneous combustion product (i.e., rxn 5.2 negligible). Field et al. (1967) estimated the rate of homogeneous CO oxidation in the char boundary layer and concluded that for a 50 μm char particle, reaction 5.3 was negligible, but for a 100 μm char particle, reaction 5.3 would contribute significantly. These early studies were supported by the work of Ayling and Smith (1972), who successfully modeled their two-color pyrometry data for 10 to 80 μm particles assuming reactions 5.2 and 5.3 were negligible.

However, later experiments by Mitchell (1988) and Waters et al. (1988a) on 100 to 160 μm char particles indicated that reaction 5.1 alone was not sufficient to account for the particle temperatures observed. The results of Mitchell and Waters et al. support the earlier theoretical conclusion of Field et al. (1967) that for larger particles CO oxidation would become important. The most illuminating work on the subject of homogeneous CO oxidation is the theoretical work of Haussmann and Kruger (date unknown), and the experimental work of Tognotti et al. (1989). Haussmann and Kruger modeled the gas phase surrounding a burning char particle with a complete set of gas phase kinetics coupled to the char combustion. Tognotti et al. analyzed the combustion products from single particle experiments in an electrodynamic balance. Both researchers concluded that the extent of CO oxidation depends on the particle size, temperature, and gas composition.

Thus, one concludes that reaction 5.2 is negligible and the importance of reaction 5.3 will depend on the char size as well as the combustion conditions.

Combustion is limited entirely by bulk mass transfer.

Combustion of small particles burning at low temperatures is expected to be significantly influenced by the intrinsic kinetics. Thus, only combustion of large particles at high temperatures is expected to occur at the bulk mass transfer limit.

O₂ dissociation may be ignored.

Energy loss is both by conduction and radiation. Energy loss by conduction is directly proportional to the "effective" thermal conductivity of the boundary layer. Hansen (1959), showed that at 3000 K, O₂ dissociation can increase the thermal conductivity of air (only 20% O₂) by a factor of almost 2. For experiments where temperatures of greater than 3000 K are achieved by increasing the O₂ level, sometimes up to 100%, O₂ dissociation may significantly increase the thermal conductivity.

5.3.1.2 Current Model

The purpose of the current model was to predict the char particle temperature and burning time for the synthetic chars used in the vaporization experiments of this work. The synthetic chars were size-classified to a mass-mean size of 130 μm , had a very narrow pore size distribution centered about 0.1 μm , had a void fraction of 0.53, and had a specific surface area of 130 m^2/g . The vaporization experiments took place in the laminar, entrained-flow reactor with a wall temperature of 1700 K, a gas temperature of 1650 K, a residence time of 0.5s, and an O₂ concentration of 10 to 80%. Char temperatures from 2000 to 3000 K were expected. In order to predict burnout times, the model had to be able to handle the initial diameter of 130 μm , as well as all smaller diameters.

Assumptions

The basic assumptions are the same as those of previous researchers which were discussed in Subsection 5.3.1.1. The controversial assumptions concerning the extent of CO oxidation, the role of the intrinsic kinetics, and the calculation of the gas phase thermal conductivity must each be addressed, as they define this model and distinguish it from all previous models.

Extent of CO oxidation.

Given the conditions of the vaporization experiments, the above review indicates that reaction 5.2 can be neglected but reaction 5.3 may be significant. Unfortunately, inclusion of gas phase kinetics for homogeneous oxidation in the boundary layer complicates this model too severely. Consequently, a lumped approach was taken where reactions 5.1 and 5.3 were added (noting that reaction 5.1 goes to completion and 5.3 does not) to give the following reaction:

where ψ = moles O_2 consumed/mole C. This reaction is assumed to occur at the char surface and the enthalpy change of reaction is given by the following equation:

$$\Delta H^\circ_{\text{rxn 4}} = 2(1-\psi) \Delta H^\circ_{\text{rxn 1}} + 2(\psi-1/2) \Delta H^\circ_{\text{rxn 2}} \quad (5.1)$$

where the enthalpy change for reactions 5.1 and 5.2 can be found in the JANAF Thermochemical Tables (Stull and Prophet, 1971). The enthalpy change for reactions 5.1 and 5.2 are nearly constant from 1700 to 3200 K and have been fit to the following functions of particle temperature, T_p :

$$\Delta H^\circ_{\text{rxn 1}} = (-8.5 \text{ J/mole K}) \times T_p + (-102,375 \text{ J/mole}) \quad (5.2)$$

$$\Delta H^\circ_{\text{rxn 2}} = (-2.9 \text{ J/moleK}) \times T_p + (-391,155 \text{ J/mole}) \quad (5.3)$$

The O_2/C ratio, ψ , is a function of char size, char temperature, and gas composition. Determination of ψ for various conditions is of obvious importance and is discussed in detail in Section 5.3.1.2.4.

Role of the intrinsic reaction kinetics.

The most appropriate kinetics found for the synthetic chars used in this work were those of Waters et al., 1988b. From measurements between 1300 and 2300 K they report that the combustion of a saran char was zero-order in O_2 , had an activation energy of 42 kcal/mole, and a pre-exponential constant of 1.33 mole/cm²s. Using these kinetic constants, intrinsic kinetics was estimated to significantly influence the reaction at particle temperatures less than 2200 K or particle diameters less than 80 μm . Given this model was to be used to model chars at temperatures as low as 2000 K and all diameters less than 130 μm , intrinsic kinetics had to be included in the model.

Calculation of thermal conductivity.

Given the combustion conditions of this work included O_2 concentrations from 10 to 80% and char particle temperatures were expected in excess of 3000 K, consideration had to be given to the effect of O_2 dissociation on the thermal conductivity of the gas in the char boundary layer. Details of the thermal conductivity estimations are given in Subsection 5.3.1.2.3.

5.3.1.2.2 Calculation Approach

The assumptions of the previous section define the model. The char particles burn independent of one another in a stagnant gas of infinite extent. Combustion is a steady state process. Carbon monoxide is the sole heterogeneous oxidation product. Homogeneous CO

oxidation is lumped with heterogeneous CO formation by means of reaction 5.4. Intrinsic kinetics must be included in the calculation of the reaction rate and O₂ dissociation must be accounted for in the thermal conductivity of the boundary layer.

5.3.1.2.2.1 Heat Balance

Given the particle is burning in steady state, the following energy balance may be written around the particle:

$$Q_{\text{gen}} = Q_{\text{loss}} \quad (5.4)$$

where:

Q_{gen} = rate of energy generation

Q_{loss} = rate of energy loss.

The rate of energy generation is simply the reaction rate multiplied by the enthalpy change of reaction.

$$Q_{\text{gen}} = J_{\text{COx}} \Delta H'_{\text{rxn } 4} \quad (5.5)$$

where J_{COx} = molar flow of CO and CO₂ away from particle.

The rate of energy generation may be rewritten in terms of the O₂ flow instead of the CO_x flow. Noting that the direction of flow of O₂ is opposite to that of the carbon oxides,

$$J_{\text{COx}} = - (1/\psi) J_{\text{O}_2} \quad (5.6)$$

where ψ = moles O₂/mole C.

From the basic assumption that the particle exists in a stagnant medium of infinite extent, the rate of energy loss is composed of two parts: conduction and radiation.

$$Q_{\text{loss}} = Q_{\text{cond}} + Q_{\text{rad}} \quad (5.7)$$

where:

Q_{cond} = rate of energy loss via conduction

Q_{rad} = rate of energy loss via radiation.

The rate of energy loss via conduction can be described as the energy flux multiplied by the area.

$$Q_{\text{cond}} = q|_r A|_r \quad (5.8)$$

where:

r = radius from center of char particle

q = energy flux

A = area.

The energy flux, q , is given by Fourier's law of conduction,

$$q = -k \nabla T \quad (5.9)$$

where

k = thermal conductivity

which when applied to our spherically symmetric problem in the absence of convection becomes

$$q = -k \, dT/dr \quad (5.10)$$

Combining Eqs. (5.10) and (5.8) gives the following differential equation

$$Q_{\text{cond}} = (-k \, dT/dr) (4\pi r^2) \quad (5.11)$$

which may be rearranged and then integrated between the surface of the particle and infinity.

at $r = r_p$, $T = T_p$, particle temperature

at $r = \infty$, $T = T_g$, gas temperature

$$Q_{\text{cond}} \int_{r_p}^{\infty} d(1/r) = 4\pi \int_{T_p}^{T_g} k \, dT \quad (5.12)$$

The thermal conductivity, k , is a function of temperature; however, if k is replaced by the appropriate constant, k_{eff} , Eq. (5.12) can be integrated to give the following algebraic equation:

$$Q_{\text{cond}} = 4\pi r_p \int_{T_g}^{T_p} k dT = 4\pi r_p k_{\text{eff}} (T_p - T_g) \quad (5.13)$$

where k_{eff} = effective thermal conductivity. The calculation of k_{eff} is discussed in detail in Subsection 5.2.3.

The rate of energy transfer between gray surfaces via radiation may be written as

$$Q_{12} = \sigma F_{12} A_1 (T_1^4 - T_2^4) \quad (5.14)$$

where:

σ	=	Stefan-Boltzmann constant
F_{ij}	=	overall interchange factor
A_i	=	external surface area of object i
T_i	=	temperature of object i.

If surface 2 completely surrounds surface 1, the overall interchange factor may be expressed as follows:

$$F_{12} = \frac{1}{(1/\epsilon_1) + (A_1/A_2)[(1/\epsilon_2) - 1]} \quad (5.15)$$

where ϵ_i = emissivity of object i.

For our system, object 1 would be the char and object 2 would be the furnace wall. Thus, $A_1 \ll A_2$, $F_{12} = \epsilon_1$, and the rate of energy transfer via radiation from the char to the furnace wall can be written as follows:

$$Q_{\text{rad}} = \sigma (4\pi r_p^2) \epsilon_p (T_p^4 - T_w^4) \quad (5.16)$$

where

r_p	=	radius of char particle
ϵ_p	=	emissivity of char particle
T_p	=	particle temperature
T_w	=	wall temperature.

Substituting Eqs. (5.6), (5.7), (5.13), and (5.16) into Eq. (5.4), the heat balance becomes:

$$\begin{aligned} J_{\text{CO}_x} \Delta H_{\text{rxn}5.4}^{\circ} &= -(1/\psi) J_{\text{O}_2} \Delta H_{\text{rxn}5.4}^{\circ} \\ &= 4\pi r_p k_{\text{eff}} (T_p - T_g) + \sigma (4\pi r_p^2) \epsilon_p (T_p^4 - T_w^4) \end{aligned} \quad (5.17)$$

At this point it is obvious that we need either J_{CO_x} or J_{O_2} as a function of T_p .

5.3.1.2.2.2 J_{CO_x} Calculated from Internal Transport and Reaction

This is the classical problem of diffusion and reaction in a porous sphere which can be found in detail in most chemical reaction engineering texts. The rate of carbon oxide flow away from the particle is equal to the product of the maximum intrinsic carbon reaction rate (R_i^{max}), the total surface area of the particle (A_p), and an effectiveness factor (η).

$$J_{\text{CO}_x} = R_i^{\text{max}} A_p \eta = R_i^{\text{max}} (S_p \rho_p V_p) \eta \quad (5.18)$$

where:

R_i^{max}	=	moles carbon consumed per unit area per unit time at the surface O_2 concentration
A_p	=	total surface area of the char particle
S_p	=	specific surface area = $130 \text{ m}^2/\text{g}$
ρ_p	=	particle density = 0.94 g/cm^3
V_p	=	particle volume = $(4/3)\pi r_p^3$
r_p	=	particle radius.

The intrinsic carbon reaction rate can be expressed in arrhenius form as follows:

$$R_i = k_i (cX_{\text{O}_2})^n = A_i \exp(-E_a/RT_p) (cX_{\text{O}_2})^n \quad (5.19)$$

where:

k_i	=	intrinsic carbon reaction rate constant
-------	---	---

A_i	=	pre-exponential constant
E_a	=	activation energy
T_p	=	particle temperature
X_{O_2}	=	mole fraction O_2
c	=	gas concentration
n	=	reaction order.

The maximum intrinsic reaction rate, $R_i^{\max}$, is simply the intrinsic rate evaluated at the surface concentration, $X_{O_2}^s$. The most appropriate intrinsic kinetics found for the chars used in this work were those of Waters et al. (1988b). From measurements between 1300 and 2300 K Waters et al. reported that the combustion of a saran char was zero-order in O_2 , had an activation energy of 42 kcal/mole, and a preexponential constant of 1.33 mole/cm² s.

The effectiveness factor, η , is a function of the dimensionless Thiele modulus, ϕ , which is a ratio of the rate of O_2 reaction to the rate of O_2 diffusion.

$$\phi = r_p \left[\frac{(1/2)k_i S_p \rho_p (cX_{O_2}^s)^{n-1}}{D_{eff}} \right]^{1/2} \quad (5.20)$$

where:

D_{eff}	=	effective diffusivity within the particle
r_p	=	particle radius
$1/2$	=	moles O_2 consumed/mole CO produced
note that k_i	=	intrinsic rate constant for <i>carbon</i> , not O_2 .

The above expression for the Thiele modulus was derived assuming equimolar counter-diffusion. A correction should be included for Stefan-flow. Assuming the only product of combustion within the char is CO, the corrected expression is as follows:

$$\phi = r_p \left[\frac{(1/2)k_i S_p \rho_p (c\gamma)^{n-1}}{D_{eff}} \right]^{1/2} \quad (5.21)$$

where

$$\gamma = \ln(1 + X_{O_2}^s).$$

The effective diffusivity is generally a combination of bulk diffusivity, which dominates in the large pores, and Knudsen diffusivity, which dominates in the small pores. However, the synthetic chars used in this work had a very narrow pore size distribution centered about $0.1 \mu\text{m}$. For a pore size of $0.1 \mu\text{m}$ and a temperature between 2000 and 3000K, the Knudsen diffusivity is always at least an order of magnitude smaller than the bulk diffusivity; therefore, bulk diffusion may be neglected. Thus, the effective diffusivity in the synthetic chars was simply the Knudsen diffusivity multiplied by the void fraction and divided by the tortuosity.

$$D_{\text{eff}} = (4/3) r_{\text{pore}} \left[\frac{2RT_p}{M_{O_2} \pi} \right]^{1/2} \left[\frac{\theta_p}{\tau_p} \right] \quad (5.22)$$

where:

$$\begin{aligned} r_{\text{pore}} &= \text{pore radius} = 0.05 \mu\text{m} \\ \theta_p &= \text{void fraction} = 0.53 \\ \tau_p &= \text{tortuosity} = 4 \\ R &= \text{ideal gas constant} \\ M_{O_2} &= \text{molecular weight of oxygen.} \end{aligned}$$

Now we have everything needed to calculate ϕ , but we need the relationship between η and ϕ in order to determine η . The functional form of the relationship between ϕ and η depends on n , the reaction order. However, at values of ϕ greater than 15, all the functional forms for a sphere approach, $\eta = 3/\phi$.

Given the physical properties of the char of interest, initial diameter of $130 \mu\text{m}$, kinetics of Waters et al. (1988b), particle temperatures as low as 2000 K, and the mole fraction oxygen at the surface as high as 0.5, ϕ was estimated to be greater than 60 for all conditions at burnouts up to 90 wt%. Thus, the asymptotic relation, $\eta = 3/\phi$, will suffice.

We now have $J_{CO_x} = f(X_{O_2}^s, T_p, \text{ and } r_p)$; however, we have introduced a new unknown, $X_{O_2}^s$. We need another equation which we will get from external mass transport.

5.3.1.2.2.3 J_{O_2} Calculated from External Transport

The flow of O_2 to the particle can be written as the molar flux multiplied by the area.

$$J_{O_2} = j_{O_2} |_r A |_r \quad (5.23)$$

where

J_{O_2} = molar flow of O_2 away from the particle.

Remembering the basic assumption that forced convection is negligible, the molar flux of O_2 may be expressed as the sum of the flux due to diffusion and that due to Stefan-flow.

$$j_{O_2} = -cD_{O_2} \left[\frac{dX_{O_2}}{dr} \right] + X_{O_2} \sum_{i=1}^m j_i \quad (5.24)$$

where:

j_i	=	molar flux of species i
D_{O_2}	=	bulk diffusive of O_2
c	=	gas concentration
X_{O_2}	=	mole fraction O_2 .

The sum of the fluxes may be expanded as follows:

$$\sum_{i=1}^m j_i = j_{O_2} + j_{N_2} + j_{CO} + j_{CO_2} \quad (5.25)$$

where:

$$j_{N_2} = 0$$

$$j_{CO} = \frac{-2(1-\psi)}{\psi} j_{O_2}$$

$$j_{CO_2} = \frac{-2(\psi-1/2)}{\psi} j_{O_2} \quad (5.26)$$

$$\psi = \text{moles } O_2 / \text{mole } C$$

$$\sum_{i=1}^m j_i = j_{O_2} \left[1 - \frac{1}{\psi} \right]$$

Substituting Eq. (5.26) back into Eq. (5.24), the O_2 flux may be rewritten as

$$j_{O_2} = \frac{-cD_{O_2}}{1-X_{O_2} \left[1 - \frac{1}{\psi} \right]} \frac{dX_{O_2}}{dr} \quad (5.27)$$

Substituting Eq. (5.27) back into Eq. (5.23), the molar flow of O_2 may be written as the following differential equation:

$$J_{O_2} = \frac{-4\pi r^2 cD_{O_2}}{1-X_{O_2} \left[1 - \frac{1}{\psi} \right]} \frac{dX_{O_2}}{dr} \quad (5.28)$$

Equation (5.28) may be rearranged and then integrated from the surface of the particle to infinity.

at $r = r_p$, $X_{O_2} = X_{O_2}^s$ = mole fraction O_2 at char surface

at $r = \infty$, $X_{O_2} = X_{O_2}^b$ = mole fraction O_2 in bulk gas.

$$\begin{aligned}
\frac{-J_{O_2}}{4\pi} \int_{r_p}^{\infty} \frac{dr}{cD_{O_2} r^2} &= \int_{X_{O_2}^s}^{X_{O_2}^b} \frac{dX_{O_2}}{1 + X_{O_2} \left[\frac{1}{\psi} - 1 \right]} \\
&= \frac{1}{\frac{1}{\psi} - 1} \ln \left[\frac{1 + X_{O_2}^b \left[\frac{1}{\psi} - 1 \right]}{1 + X_{O_2}^s \left[\frac{1}{\psi} - 1 \right]} \right]
\end{aligned} \tag{5.29}$$

At this point one recognizes that cD_{O_2} is a function of temperature which is a function of r . Fortunately, cD_{O_2} is a well-behaved function that varies only slightly ($cD_{O_2} = 27 \times 10^{-6}$ mole/cm s at $r = \infty$ where the gas temperature = 1650 K and is never expected to be greater than 41×10^{-6} mole/cm s which is for gas temperature = 3200 K). Therefore, a mean value for cD_{O_2} , taken at $T_m = (T_g + T_p)/2$, was assumed to sufficiently model the boundary layer.

Thus, the integral on the left side of equation (5.29) may be integrated to give the following equation:

$$J_{O_2} = -\frac{4\pi r_p \overline{cD_{O_2}}}{\frac{1}{\psi} - 1} \ln \left[\frac{1 + X_{O_2}^b \left[\frac{1}{\psi} - 1 \right]}{1 + X_{O_2}^s \left[\frac{1}{\psi} - 1 \right]} \right] \tag{5.30}$$

where $\overline{cD_{O_2}} = cD_{O_2}$ evaluated at T_m .

Equation (5.30) can be rewritten in terms of the mole fraction O_2 at the char surface:

$$X_{O_2}^s = \frac{\exp \left[\ln \left[1 + X_{O_2}^b \left[\frac{1}{\psi} - 1 \right] \right] + \frac{J_{O_2} \left[\frac{1}{\psi} - 1 \right]}{4\pi r_o \overline{cD_{O_2}}} \right] - 1}{\frac{1}{\psi} - 1} \tag{5.31}$$

5.3.1.2.2.4 Algorithm

The energy balance from Subsection 5.3.1.2.2.1 produced Eq. (5.17) which gives $T_p = f(J_{CO_x}, r_p, T_g, \psi)$. The internal transport and reaction described in Subsection 5.3.1.2.2.2 produced Eq. (5.18) which gives $J_{CO_x} = f \left[X_{O_2}^s, T_p, r_p \right]$. The external transport described in Subsection 5.3.1.2.2.3 produced Eq. (5.31) which gives $X_{O_2}^s = f \left[J_{O_2}, T_p, T_g, X_{O_2}^b, \psi, r_p \right]$. A fourth Eq. (5.6) can be written to relate J_{O_2} to J_{CO_x} through the stoichiometry of the oxidation reaction. Thus, there are four equations and eight variables (J_{O_2} , J_{CO_x} , T_p , T_g , r_p , ψ , $X_{O_2}^s$, $X_{O_2}^b$).

The gas temperature and mole fraction oxygen in the bulk were fixed. The char was assumed to burn in pseudo steady-state; therefore, the particle radius was fixed. The reaction stoichiometry, ψ , was chosen empirically (see Subsection 5.3.1.2.4). This leaves four unknowns: T_p , J_{O_2} , J_{CO_x} , and $X_{O_2}^s$.

Unfortunately, an explicit solution to the above four equations was not possible. An iterative approach was taken and is illustrated in Figure 5.3-1. The calculation algorithm began with the input of the bulk oxygen concentration, the particle size, and the O_2/C ratio. The particle temperature and oxygen concentration at the char surface were then assumed. With these inputs and assumptions, along with the kinetics of Waters et al. (1988b), the reaction rate was calculated by means of Eq. (5.18). The reaction rate was then related to the oxygen flow, J_{O_2} , by means of Eq. (5.6). This oxygen flow was then used in Eq. (5.31) to calculate the oxygen concentration at the char surface. The original assumed value for the oxygen concentration at the char surface was then compared to the calculated value. If the values were not close enough, a new value was assumed and the process was repeated. If the values were sufficiently close, then, for that temperature, the oxygen concentration at the char surface was correct.

The next step was to determine if the assumed temperature was correct. The energy generation rate was calculated from the previously determined reaction rate using Eq. (5.5). A second temperature was assumed and the rate of energy loss, based on the second assumed temperature, was calculated from Eq. (5.7). The second temperature was increased until the heat balance was satisfied and the rate of energy loss was equal to the rate of energy generation. If the temperature which satisfied the heat balance was not sufficiently close to the original assumption for particle temperature, then a new particle temperature was assumed and the entire process was repeated. If the two temperatures were close enough to satisfy the convergence criteria, then the calculation was complete.

C-1692

FIGURE 5.3-1. - Temperature calculation algorithm.

Two of the model inputs have not yet been sufficiently defined: the effective thermal conductivity of the boundary layer and the O_2/C ratio. These inputs are the subjects of the next two sections.

5.3.1.2.3 Effective Thermal Conductivity of the Boundary Layer

Equation (5.13), which defined the effective thermal conductivity,

$$Q_{\text{cond}} = 4\pi r_p \int_{T_g}^{T_p} k dT = 4\pi r_p k_{\text{eff}}(T_p - T_g)$$

may be rewritten as

$$k_{\text{eff}} = \frac{\int_{T_g}^{T_p} k dT}{T_p - T_g}$$

Obviously we need k as a function of T in order to find $k_{\text{eff}} = f(T_p \text{ and } T_g)$. In order to accurately determine $k = f(T)$, we must consider the effects of O_2 dissociation.

In all conduction problems, a temperature gradient exists. If the temperature gradient occurs in a gas mixture which is in chemical equilibrium, the equilibrium, and hence the gas composition may change along the temperature gradient. As diffusion and conduction occur along the temperature gradient, some chemical energy, as well as thermal energy, may be transported along the gradient. Thus, the thermal conductivity of a gas mixture will be increased if a temperature sensitive reaction exists in equilibrium along the temperature gradient. The reaction of interest in a mixture of O_2 and N_2 at temperatures between 1650 and 3200 K is O_2 dissociation.

Butler and Brokaw (1957) report that the thermal conductivity of a reacting gas mixture in chemical equilibrium is the sum of the hypothetical thermal conductivity of the gas mixture without the reaction, k_n , and the thermal conductivity due to the reaction, k_r

$$k = k_n + k_r \quad (5.33)$$

The thermal conductivity of a nonreactive gas mixture is not usually a linear function of the mole fraction. If the molecules are polar, the thermal conductivity is generally larger than would be predicted from a mole fraction average. If the molecules have large differences in molecular weight, the thermal conductivity is generally less than would be predicted from a mole fraction average. The gases of interest in this study are mixtures of O_2 and N_2 which are both nonpolar and have similar molecular weights. Thus, a mole fraction average should closely approximate the hypothetical thermal conductivity of the gas without reaction.

$$k_n = X_{O_2}^b k_{O_2} + X_{N_2}^b k_{N_2}$$

where:

X_i^b = mole fraction species i without dissociation

k_i = thermal conductivity of pure i without dissociation.

In order to calculate k_n , pure component thermal conductivities for molecular nitrogen and molecular oxygen were required. Nitrogen does not disassociate significantly at 1 atm of pressure until the temperature exceeds 4000 K. Thus, the pure component thermal conductivity of N_2 can be measured directly and was taken from the National Bureau of Standards publication NSRDS-NBS 8 by Powell et al., 1966. The thermal conductivity ranged from 0.95×10^{-3} J/cm s K at 1700 K to 1.74×10^{-3} J/cm s K at 3200 K.

Oxygen begins to disassociate significantly at temperatures as low as 2200 K at 1 atm of pressure. The thermal conductivity of molecular O_2 without dissociation is hypothetical at temperatures greater than 2200 K and, thus, cannot be measured. The hypothetical thermal conductivity of molecular oxygen was calculated by the method of Chung et al. (1984). The method of Chung et al. requires the gas molecular weight, acentric factor, viscosity, and heat capacity. The heat capacity of molecular oxygen was taken from the JANAF Thermochemical Tables (Stull and Prophet, 1971) and the viscosity of molecular oxygen was calculated using the Chapman-Enskog equation with the Leonard-Jones intermolecular force law. The acentric factor and the Leonard-Jones parameters were taken from Reid et al. (1987). The thermal conductivity of molecular O_2 was calculated to be 1.10×10^{-3} J/cm s K at 1700 K and 1.79×10^{-3} J/cm s K at 3200 K, very close to the values for molecular N_2 .

The reactive thermal conductivity was given by Butler and Brokaw (1957) as the following:

$$k_r = \frac{R \left[T \frac{d \ln K}{dT} \right]^2}{\sum_{j=1}^{\mu-1} \sum_{m=j+1}^{\mu} \left[\frac{RT}{D_{mj}P} \right] \left[\frac{(a_j X_m - a_m X_j)^2}{X_m X_j} \right]}$$

where

- μ = total number of species = 3 (O_2 , N_2 , O)
- D_{mj} = diffusivity of species m in species j
- R = ideal gas constant
- T = temperature
- K = equilibrium constant for reaction 5.5
- a_j = stoichiometric coefficient for species i in reaction 5.5 ($a_{N_2}=0$, $a_{O_2}=-1$, $a_O=2$)
- X_i = mole fraction species i .

When applied to reaction 5.5, the denominator of Eq. (5.35) expands to the following expression:

$$\frac{1}{D_{O-O_2}} \frac{(X_O + 2X_{O_2})^2}{X_O X_{O_2}} + \frac{1}{D_{N_2-O_2}} \frac{X_{N_2}}{X_{O_2}} + \frac{1}{D_{N_2-O}} \frac{4X_{N_2}}{X_O}$$

and numerator of Eq. (5.35) may be rewritten as:

$$\frac{(\Delta H_{rxn \ 5.5})^2}{RT^2}$$

The mole fractions of each species, the diffusivities, and the change in enthalpy of reaction 5.5 are all functions of temperature. The mole fractions of each species are also a function of the initial gas composition before dissociation. The change in enthalpy of reaction 5.5 was calculated from data taken from the JANAF Thermochemical Tables (Stull and Prophet, 1971). The diffusivities were calculated using the Chapman-Enskog equation with the Leonard-Jones intermolecular force law.

In order to determine the mole fractions of each species, one can write the following six equations:

$$X_O \equiv n_O/n_t \quad (5.36)$$

$$X_{O_2} \equiv n_{O_2}/n_t \quad (5.37)$$

$$X_{N_2} \equiv n_{N_2}/n_t \quad (5.38)$$

$$n_t \equiv n_O + n_{O_2} + n_{N_2} \quad (5.39)$$

$$n_{O_2}^0 = n_{O_2} + 1/2 n_O \quad (5.40)$$

$$K = X_O^2/X_{O_2} \quad (5.41)$$

where:

n_i	=	moles of species i
n_t	=	total moles
n_i^0	=	initial moles of species i without dissociation
X_i	=	mole fraction species i
K	=	equilibrium constant for reaction 5.5.

Equations (5.36) through (5.39) are simply definitions, Eq. (5.40) represents conservation of O atom, and Eq. (5.41) represents chemical equilibrium. These equations may be solved to give the mole fraction of each species as a function of the equilibrium constant and the mole fraction O_2 in the bulk (i.e., without dissociation).

$$X_O = \left[\frac{1}{16} K^2 + \frac{1}{8} K^2 X_{O_2}^b + \frac{1}{16} K^2 X_{O_2}^{b2} + K X_{O_2}^b \right]^{1/2} - K \left[1 + X_{O_2}^b \right] / 4 \quad (5.42)$$

$$X_{O_2} = X_O^2/K \quad (5.43)$$

$$X_{N_2} = 1 - X_O - X_{O_2} \quad (5.44)$$

The equilibrium constant was determined as a function of temperature from data taken from the JANAF Thermochemical Tables.

We now have all the necessary equations to estimate the thermal conductivity from Eq. (5.33) as a function of both temperature and initial mole fraction oxygen. Table 5.3-1 shows a sample of those calculated thermal conductivities. The thermal conductivity ranges from 0.96×10^{-3} J/cm s K for 5% O_2 in N_2 at 1700 K to 9.39×10^{-3} J/cm s K for 100% O_2 at 3200 K. A comparison of the above thermal conductivities calculated with accounting for O_2 dissociation (k) to the thermal conductivity calculated without accounting for O_2 dissociation (k_n) is shown in Figure 5.3-2 which is a plot of k/k_n versus temperature. Figure 5.3-2 illustrates the lack of importance of O_2 dissociation on char particles burning in 10% O_2 which are not expected to achieve temperatures greater than 2000 K. However, for chars burning at 100% O_2 , particle temperatures are expected to exceed 3000 K, in which case O_2 dissociation will clearly have a significant influence on the thermal conductivity of the boundary layer.

TABLE 5.3-1. - Thermal conductivity as a function of temperature and oxygen concentration

Tempertaure (K)	Thermal Conductivity x 10^3 (J/cm s K)							
	5% O_2	10% O_2	20% O_2	30% O_2	50% O_2	65% O_2	80% O_2	100% O_2
1700	0.96	0.97	0.98	1.00	1.03	1.05	1.07	1.10
1800	1.02	1.03	1.04	1.06	1.09	1.11	1.13	1.16
2000	1.16	1.17	1.19	1.20	1.23	1.25	1.27	1.29
2200	1.31	1.33	1.36	1.38	1.42	1.45	1.48	1.51
2400	1.47	1.53	1.60	1.66	1.75	1.81	1.87	1.93
2600	1.71	1.83	1.99	2.12	2.33	2.46	2.58	2.73
2800	2.05	2.29	2.63	2.90	3.32	3.59	3.83	4.12
3000	2.46	2.91	3.55	4.05	4.85	5.35	5.79	6.33
3200	2.83	3.57	4.65	5.50	6.86	7.71	8.47	9.39

FIGURE 5.3-2. - Effect of oxygen dissociation on thermal conductivity.

This brings us back to the purpose of this section which was to determine the effective thermal conductivity of the boundary layer as described in Eq. (5.32).

$$k_{\text{eff}} = \frac{\int_{T_g}^{T_p} k dT}{T_p - T_g} \quad (5.32)$$

Equation (5.32) was numerically integrated using the above calculated values for $k = f(X_{\text{O}_2}^b, T)$ to give $k_{\text{eff}} = f(X_{\text{O}_2}^b, T_g, T_p)$. The bulk gas temperature, T_g , was 1650 K in all experiments. For purposes of modeling, k_{eff} was fit to a fifth order polynomial function of T_p for each value of $X_{\text{O}_2}^b$. The coefficients of the polynomial for a few select values of $X_{\text{O}_2}^b$ are given in Table 5.3-2.

TABLE 5.3-2 - Coefficients for the calculation of the effective thermal conductivity of the boundary layer

% Oxygen	Coefficients for $K_{eff} = A + BT_p^2 + CT_p^2 + DT_p^3 + ET_p^4 + FT_p^5$					
	A x 10 ²	B x 10 ⁵	C x 10 ⁵	D x 10 ¹²	E x 10 ¹⁵	F x 10 ¹⁹
5	0.9466	-1.9744	1.7523	-7.5368	1.5910	-1.3091
10	1.0276	-2.1580	1.9166	-8.2454	1.7342	-1.4101
20	1.0865	-2.2911	2.0364	-8.7539	1.8293	-1.4603
30	1.1057	-2.3344	2.0770	-8.9226	1.8549	-1.4586
35	1.1099	-2.3440	2.0866	-8.9617	1.8589	-1.4518
50	1.1072	-2.3385	2.0857	-8.9545	1.8464	-1.4150
65	1.0910	-2.3028	2.0587	-8.8392	1.8132	-1.3652
80	1.0683	-2.2525	2.0189	-8.6719	1.7706	-1.3102
100	1.0297	-2.1672	1.9504	-8.3861	1.7023	-1.2307

5.3.1.2.4 Choice of O₂/C Ratio

As discussed in the review of previous work in Subsection 5.3.1.1.2, heterogeneous CO₂ formation is negligible under the conditions of interest; however, CO oxidation in the boundary layer may be significant depending on the particle size and combustion conditions. In Subsection 5.3.1.2.1 a lumped approach was outlined to handle the heterogeneous CO formation and homogeneous CO oxidation as one reaction occurring at the char surface.

The model was developed with, ψ , the O₂/C ratio in the lumped reaction as a variable. The O₂/C ratio is the last remaining input required for this model and must be determined empirically. Thus, a further review of the literature is required. As mentioned in Subsection 5.3.1.1.2, Haussmann and Kruger (19??) modeled the gas phase surrounding a burning char particle with a complete set of gas phase kinetics coupled to the char combustion. They reported the dependence of particle temperature on radius, oxygen concentration, water concentration, and gas temperature. Unfortunately, their work was strictly theoretical, they reported only how the above variables influenced the particle temperature, with no mention of the extent of CO oxidation, and they only considered oxygen concentrations up to 25%.

Waters et al. (1988a) performed experimental work on spherical carbon particles between 100 and 160 μm . The particles were burned in 12 to 36% O_2 and 14 to 20% H_2O , at a gas temperature of 1775 K. The particles achieved temperatures of 1400 to 2200 K. In order to account for the observed particle temperatures, homogeneous CO oxidation was assumed to occur in the boundary layer. In order to model the CO oxidation in the boundary layer, Waters et al. fit their results using an adjustable parameter which represented the fraction of the energy released from a hypothetical complete CO oxidation. The best fit of this parameter to all their experimental data was 0.35. This is virtually the same approach as taken in the model developed in this work. Their value of 0.35 corresponds to $\psi = 0.5 + 1/2(0.35) = 0.675$. Unfortunately, they fit all their data for all their conditions to a single parameter, neglecting the expected dependence of the parameter on gas concentration and particle temperature. Furthermore, their experiments were run in gases with extremely high water contents, which, given the importance of H_2O catalysis in homogeneous CO oxidation, makes their results completely inapplicable to the experiments of this work, which were run dry.

As mentioned in Subsection 5.3.1.1.2, Tognotti et al. (1989) analyzed the combustion products from single particle experiments in an electrodynamic balance. Tognotti et al. directly measured the CO_2/CO ratio after complete combustion of 180 to 240 μm spherical particles. Tognotti et al. were able to experimentally verify the importance of the water content and particle temperature on the CO_2/CO ratio. The CO_2/CO ratio was at a minimum of approximately 0.1 at a particle temperature of 1500 K. The CO_2/CO ratio increased at lower temperatures due to heterogeneous CO formation and at higher temperatures due to homogeneous CO oxidation. In the environment of 20% O_2 , no added water, and a particle temperature of 2000 K, 15% of the CO was oxidized ($\psi = 0.5 + 1/2 \times 0.15 = 0.575$). In the environment of 100% O_2 and no added water, the Tognotti et al. results only cover particle temperatures from 2000 to 2500 K. If the results are extrapolated to 3000 K, approximately 70% of the CO would be expected to oxidize ($\psi = 0.5 + 1/2 \times 0.7 = 0.85$). These conditions of no water, 2000 K with 20% O_2 , and 3000 K with 100% O_2 are approximately what was expected in the experiments of this work. Unfortunately, three problems develop when trying to incorporate the Tognotti et al. data into the model of this work. First, the particle sizes were different. The work experiments were performed with 130 μm chars and the Tognotti et al. data was collected using 180-240 μm chars. The size of the char is directly proportional to the size of the boundary layer. Consequently, the extent of CO oxidation in the boundary layer is a strong function of particle size (Field et al., 1967). Second, the data exist only at 20 and 100% O_2 . Third, the data are the integrated sum of the CO and CO_2 produced over the entire burnout, but the model of this work is for a single char radius burning under pseudo steady-state conditions.

The data of Tognotti et al. were the most applicable; therefore, each of the above problems was addressed as well as possible.

Effect of char particle size.

In order to correct the Tognotti et al. data for the smaller particles used in this work, the relation between the O_2/C ratio (ψ) and the char radius (r_p) was required. Haussmann and Kruger (1977), reported the increase in particle temperature due to homogeneous CO oxidation (ΔT_p) was approximately proportional to r_p^2 . In order to use this relation, the relationship between ΔT_p and ψ was required. The model developed in the previous sections was used to determine the relation between ΔT_p and ψ . Figure 5.3-3 shows how the predicted particle temperature increased as ψ was increased from the minimum value of 0.5 ($\psi = 0.5$ corresponds to no CO oxidation). Figure 5.3-3 shows the model results for a $130\ \mu\text{m}$ char particle at both 20 and 100% O_2 . The increase in particle temperature, ΔT_p , was approximately proportional to $(\psi - 0.5)^{0.7}$. Thus, if we combine this result with the relation between ΔT_p and ψ from Haussmann and Kruger, the following equation may be written:

$$(\psi - 0.5)^{0.7} \propto r_p^2 \quad (5.45)$$

FIGURE 5.3.3. - Effect of the O_2/C ratio on the predicted particle temperature.

Using Eq. (5.45), the data of Tognotti et al. were corrected to particles of $130\text{ }\mu\text{m}$ to give $\psi = 0.52$ at 20% O_2 and 2000 K, and $\psi = 0.59$ at 100% O_2 and 3000 K.

Data exist only at 20 and 100% O_2 . Lacking a better method of extrapolation, the data at 20 and 100% O_2 were linearly extrapolated to other O_2 concentrations. Thus, values of ψ of 0.507, 0.511, 0.520, 0.529, 0.546, 0.573, and 0.590 were used for O_2 concentrations of 5, 10, 20, 30, 50, 80, and 100% O_2 , respectively.

Data are from complete burnout.

The model of this work is for a char of constant size burning in pseudo steady-state; therefore, data for CO/CO_2 ratio as a function of burnout would be desirable. Unfortunately, the Tognotti et al. data are the integrated sum of the CO and CO_2 produced over the entire burnout and differentiation of that data seems impossible. However, since the model was to be used at the initial radius and then incrementally smaller radii to simulate burnout (see Table 5.3-3), the values of ψ determined from the Tognotti data were simply assumed to remain constant all through burnout.

Clearly, the choice of ψ has been difficult and a sensitivity analysis is in order. Figure 5.3-3 is a sensitivity analysis. At 20% O_2 a value of ψ of 0.52 was chosen. This corresponds to 4% of the CO oxidized to CO_2 in the boundary layer. The error in the predicted temperature if the actual percentage of CO oxidized is 1/2 or twice the estimated 4% is +15 or -50K, respectively. At 80% O_2 a value of ψ of 0.573 was chosen. This corresponds to approximately 15% of the CO oxidized to CO_2 in the boundary layer. The error in the predicted temperature if the actual percentage of CO oxidized is 1/2 or twice the estimated 15% is +60 or -115 K, respectively.

5.3.1.2.5 Model Results

Given the calculations for the effective thermal conductivity in Subsection 5.3.1.2.3 and the estimates for the O_2/C ratios in Subsection 5.3.1.2.4, the model was complete.

In order to simulate char burnout, the model was used to calculate the char temperature and burning rate for the initial diameter of $130\text{ }\mu\text{m}$ and 12 subsequent diameters. The results for two combustion conditions, 10 and 80% O_2 , are shown in Table 5.3-3. As seen in Table 5.3-3, the particle temperature reaches a maximum at an intermediate diameter. This can be explained by considering the dependence of the energy generation and energy loss on char particle size. When a particle is very large, combustion is limited by bulk mass-transfer, energy generation is proportional to r_p , and energy loss is proportional to between r_p^2 and r_p , depending on the relative importance of radiation and conduction. Thus, when combustion is limited by bulk mass-transfer, the pseudo-steady-state particle temperature increases as the particle size decreases. As combustion proceeds, the particle shrinks, and as the particle shrinks it moves toward the kinetic regime. As chemical kinetics and internal mass-transfer begin to limit combustion, the energy generation rate is proportional to between r_p^2 and r_p^3 , depending on the effectiveness factor. The energy loss

TABLE 5.3-3. - Model results as a function of diameter for
10 and 80% oxygen

Particle Diameter (μm)	Particle Temperature (K)	O ₂ Concentration at Char Surface (%)	Effectiveness Factor	Reaction Rate (gmolC/s)	Mass Fraction Burned	Incremental Burn Time (s)
10% O ₂ , O ₂ /C ratio = 0.511						
130	1970	2.2	0.010	3.52×10^{-7}	0	0
120	1975	2.4	0.011	3.18×10^{-7}	0.2135	0.057
110	1970	2.7	0.012	2.80×10^{-7}	0.3942	0.054
100	1965	3.0	0.015	2.41×10^{-7}	0.5448	0.052
90	1960	3.4	0.107	2.07×10^{-7}	0.6682	0.050
80	1945	4.0	0.022	1.67×10^{-7}	0.7670	0.048
70	1925	4.6	0.029	1.31×10^{-7}	0.8439	0.047
60	1895	5.5	0.041	9.51×10^{-8}	0.9017	0.046
50	1865	6.3	0.507	6.50×10^{-8}	0.9431	0.047
40	1820	7.3	0.089	3.90×10^{-8}	0.9709	0.048
30	1775	8.0	0.145	1.99×10^{-8}	0.9877	0.052
20	1730	8.5	0.263	7.81×10^{-9}	0.9964	0.056
10	1690	9.0	0.617	1.78×10^{-9}	0.9995	0.060
0	—	—	—	—	1.0	0.046
Total burn time = 0.662						
80% O ₂ , O ₂ /C ratio = 0.573						
130	3050	3.7	0.002	2.82×10^{-6}	0	0
120	3070	4.2	0.002	2.59×10^{-6}	0.2135	0.007
110	3085	4.7	0.002	2.36×10^{-6}	0.3942	0.007
100	3100	5.5	0.002	2.13×10^{-6}	0.5448	0.006
90	3115	6.5	0.003	1.89×10^{-6}	0.6682	0.006
80	3125	7.7	0.003	1.65×10^{-6}	0.7670	0.005
70	3130	9.5	0.004	1.40×10^{-6}	0.8439	0.005
60	3130	12.0	0.006	1.15×10^{-6}	0.9017	0.004
50	3110	15.9	0.008	8.88×10^{-7}	0.9431	0.004
40	3070	21.7	0.012	6.32×10^{-7}	0.9709	0.003
30	2965	31.8	0.021	3.75×10^{-7}	0.9877	0.003
20	2660	50.8	0.060	1.38×10^{-7}	0.9964	0.003
10	1800	77.0	1.0	6.51×10^{-9}	0.9995	0.004
0	—	—	—	—	1.0	0.013
Total burn time = 0.069						

is still proportional to between r_p^2 and r_p . Thus, the pseudo-steady-state particle temperature decreases as the particle size decreases. Consequently, a maximum char temperature is achieved just as the particle shrinks out of the bulk mass-transfer limited combustion regime.

The burning rate reported in Table 5.3-3 was used to calculate the incremental burning time for each increment in particle size. The incremental burn times were then summed to give the total burnout time. Two differently weighted average temperatures, the maximum temperature, the total burn time, and a 'vaporization burn time' are summarized in Table 5.3-4 for a range of O_2 concentrations. The first average reported was time-weighted over complete burnout. This average was very sensitive to the long, and relatively cool, final stages of burnout. A second average was required for the interpretation of the vaporization data presented in the following section. The vaporization which occurs during any incremental stage of burnout is directly proportional to both the burn time for that increment and the volume of total char remaining as that increment burns. The vaporization is also inversely proportional to the diffusion length or radius. Thus, a time- and r_p^2 -weighted average was desired. However, vaporization is also an exponential function of particle temperature and an unknown function of the reducing atmosphere within the particle. Thus, only that fraction of burnout which occurred with an effectiveness factor of less than

TABLE 5.3-4. - Summary of model results

Mole Fraction Oxygen	$O_2:C$ Ratio	Average ¹ Particle Temperature (K)	Average ² Particle Temperature (K)	Maximum Particle Temperature (K)	Total Burn Time (s)	Vaporization Burn Time ³ (s)
0.05	0.507	1782	1832	1835	1.222	0.4
0.10	0.511	1871	1959	1975	0.662	0.4
0.20	0.520	2057	2243	2260	0.319	0.197
0.30	0.529	2240	2493	2530	0.198	0.130
0.35	0.533	2317	2594	2635	0.166	0.108
0.50	0.546	2513	2822	2870	0.112	0.075
0.65	0.559	2679	2974	3020	0.084	0.063
0.80	0.573	2793	3087	3130	0.069	0.052
1.00	0.590	2894	3201	3235	0.057	0.044
¹ Time-weighted average over complete burnout ² Time-and-radius-squared-weighted average while effectiveness factor < 0.1 and burn time $< 0.4s$ (hot zone of furnace only 0.4s) ³ Burn time in furnace while effectiveness factor < 0.1 (hot zone of furnace only 0.4s)						

0.1 was considered in the average. Furthermore, the hot zone in the furnace used in the vaporization experiments was only 0.4s. Thus, this average was performed only over the first 0.4s of burnout, if it lasted that long. This average is much greater than the time-only-weighted averages and only slightly less than the maximum temperature.

The 'vaporization burn time' was the burn time while the char particle had an effectiveness factor of less than 0.1 and was still in the hot zone of the furnace (i.e., maximum burn time of 0.4s).

5.3.1.3 Comparison of Model Results to Data from Timothy et al. (1982)

In order to check the model results, particularly the effect of the corrected thermal conductivity, a comparison to data was sought. The combustion temperature data of Timothy et al. (1982) was the most appropriate for comparison because it was generated under nearly the same combustion conditions that the model was developed to cover: O_2 concentrations up to 100% and gas temperatures of approximately 1650 K. In addition, the data of Timothy et al. was collected using the same size chars. In fact, the only significant difference was that the Timothy et al. data was collected from the combustion of coals, not synthetic chars. Timothy et al. measured the char combustion temperatures using a two-color pyrometer with a laminar, entrained-flow reactor. The two-color pyrometer was set up to view the particles through the feeder probe. The particles remained in view of the pyrometer all through burnout; thus, temperature data could be collected for the entire burnout. Figure 5.3-4 shows the data collected by Timothy et al. (1982) for two different coals: Montana lignite and Illinois #6 bituminous coal. The temperature shown was a time-weighted average over complete burnout. Also shown is the Timothy et al. model assuming bulk gas diffusion limited combustion based on initial diameter with no accounting for O_2 dissociation. The model over-predicted the data at O_2 concentration greater than 50% because O_2 dissociation was not included, and under-predicted the data at O_2 concentrations less than 50% because the assumption of strict bulk mass-transfer limited combustion breaks down and reaction kinetics become important. The difference between the Montana lignite and Illinois #6 bituminous coal was never completely explained, especially at the higher O_2 concentrations where combustion was expected to be limited by bulk gas diffusion only. The key to explaining the Timothy et al. data is to note how the temperatures were averaged. As seen in the results from the model of this thesis (Table 5.3-3), the particle temperature falls off dramatically in the later stages of burnout. This temperature decline in the later stages of burnout happens because the particle shrinks and approaches the kinetic regime. The importance of this temperature decline depends on how the temperature is averaged. With this in mind, the Timothy et al. model and data was reconsidered. The Timothy et al. model was clearly a maximum temperature, not a time-weighted average temperature, because it was based on the initial diameter only. Conversely, the temperature reported for the coals was a time-weighted average temperature. However, the coals burned out differently. Illinois #6 bituminous coal particles swell, form a cenosphere, and burn out as a shell. If an Illinois #6 bituminous coal particle had a swelling ratio of 1.15 and a mass loss of 35 wt% on devolatilization, it would burn out as a shell from 150 to 125 μm , all of which would occur at approximately the maximum temperature. Thus, the time-weighted average

FIGURE 5.3-4. - Temperature versus oxygen concentration, comparison to Timothy et al., 1982.

temperature for the Illinois #6 bituminous coal would be very close to the maximum temperature. Montana lignite, on the other hand, burns as a shrinking core; therefore, its time-weighted average temperature would be substantially less than its maximum temperature. This explains the differences between the data from the Illinois #6 bituminous coal and that from the Montana lignite. A model based on the maximum temperature was expected to fit the Illinois #6 bituminous coal temperatures and a model based on the time-averaged temperature was expected to fit the Montana lignite temperatures. Figure 5.3.4 shows that, indeed, this is the case. Given that the current model uses the combustion kinetics for a synthetic char, an effective diffusivity based on a strictly microporous synthetic char, and does not account for the increase in diameter due to swelling in the bituminous coal, the current model fits both sets of coal char data remarkably well. In conclusion, the current model of char combustion is believed to produce char particle temperatures and burn times at least as accurately as they could have been measured by two-color pyrometry in the laminar, entrained-flow reactor. Furthermore, reinterpretation of the Timothy et al. (1982) data emphasizes the importance of understanding what temperature to use for interpretation of the vaporization data in the next section.

For comparison, peak particle temperatures in a coal-fired utility boiler vary with coal rank and are generally in the range 1700 to 2200 K. These temperatures are 100 to 300 K hotter than the surrounding gas temperature (Smoot and Smith, 1985). Coal particle temperatures examined in this program include this range as well as higher temperatures so that fundamental ash formation mechanisms may be evaluated.

5.3.2 Vaporization Results and Modeling

The objectives of the submicron ash formation research were to determine the following:

1. Is vaporization the principal mechanism whereby metal oxides end up in the submicron ash?
2. If so, what are the vaporization mechanisms?
3. How do mineral interactions affect the vaporization process?

In order to make this problem tractable, the scope has to be limited to the most important chemical species. For this work, iron, silicon, and calcium were chosen for study.

Two size-classified coals, seven size-classified sucrose/carbon black chars, and the two size-classified, density-separated extraneous pyrite samples were used in the vaporization experiments. The experiments were conducted in the laminar, entrained-flow reactor described in Subsection 5.2.2. The cascade impactor described in Subsection 5.2.3 was used to aerodynamically size-classify the combustion aerosol. The cellulose acetate/nitrate absolute filter described in Subsection 5.2.3 was used to collect the submicron ash. The ash, coal, synthetic char, and pyrite samples were chemically analyzed by inductively-coupled plasma emission spectroscopy (ICPES).

5.3.2.1 Sample Preparation

5.3.2.1.1 Coals

The raw coals were size classified in order to prevent problems feeding samples to the laminar, entrained-flow reactor, remove fines, facilitate modeling, and simplify the comparison of results from different coals and chars.

Size-classification was accomplished using a Donaldson Acucut centrifugal air-classifier and a Ro-tap sieving machine. Centrifugal air-classification had a high level of dispersive energy making it an effective method of fines removal; however, it was a poor method for producing a narrowly sized sample because significant grinding occurred during classification. Therefore, centrifugal air-classification was used for the first size-classification step as a method to remove particles less than 40 μm . Centrifugal air-classification not only removed fines, but also dramatically improved sieve performance. Sieves with openings of 105 and 90 μm were then used to produce a narrow particle size distribution which, when measured by laser light diffraction, had a volume mean and standard deviation of 130 and 8 μm , respectively.

Because the above size-classified coals were to be used for submicron ash formation studies it was essential that any fines present in the samples did not contribute significantly to

the submicron ash produced. In order to determine the contribution to the submicron ash from fines, a coal sample was prepared as described in the previous section, split into two equal portions, and one portion was further classified by wet-sieving with sonication. This technique was particularly effective in removing fines attached to larger particles. Both samples were then burned under identical conditions in the laminar, entrained-flow reactor and the resulting aerosols were collected using all eight stages of the cascade impactor (see Subsection 5.2.3). No differences were detected between the ash particle size distributions; therefore, fines in these samples made a negligible contribution to the submicron ash.

Realizing that coal size and coal composition are not independent, the ash composition of the size-classified coals was also determined and is reported in Table 5.3-5. These analyses were accomplished with inductively coupled plasma emission spectroscopy (ICPES) because this was the analysis of choice for the submicron ash. As is shown in Tables 5.3-5 and 5.3-6, the raw coals have approximately 40 to 60% more ash than the size-classified coals. The raw and size-classified coals have similar relative compositions with only small differences which can easily be explained as a lower relative concentration of clay particles in the size-classified sample.

TABLE 5.3.5. - Ash composition of the 90 to 106 μ m coal samples as determined by inductively coupled plasma emission spectroscopy

Ash Composition (wt% of ash)	Kentucky #9 Bituminous Coal	N.D. Beulah Lignite
Ash content ¹ (wt% of coal)	9.3	8.0
K ₂ O	2.4	1.1
Na ₂ O	0.5	9.6
MgO	<1.0	6.4
CaO	2.7	20.0
Fe ₂ O ₃	22.2	21.7
Al ₂ O ₃	18.7	14.6
SiO ₂	53.5	26.7
¹ Ash content was determined by summing the ICPES analysis for the seven elements listed. All elements were assumed to be present as the oxide.		

TABLE 5.3.6. - ASTM ash analysis of the raw Phase I coals presented on a sulfur-free basis

Ash Composition (wt% of ash)	Kentucky #9 Bituminous Coal	N.D. Beulah Lignite
Ash content ¹ (wt% of coal)	14.9	10.9
K ₂ O	2.7	0.4
Na ₂ O	0.9	7.7
MgO	1.2	5.3
CaO	3.3	21.7
Fe ₂ O ₃	23.5	15.5
Al ₂ O ₃	21.6	18.4
SiO ₂	46.8	27.4
¹ ASTM ash on an SO ₃ free basis. Data from Boni et al., 1990.		

5.3.2.1.2 Synthetic Chars

Synthetic chars were produced for use in vaporization studies because they provided a method to isolate the behavior of any particular mineral or set of minerals. In addition, synthetic chars made possible the control of the mineral content and size which further simplified modeling efforts and results comparisons. Synthetic chars were also used to produce submicron ash of controlled composition.

A wide variety of synthetic chars and manufacturing procedures were investigated. Each char that was considered was manufactured in the pyrolysis furnace described earlier in Subsection 5.2.1. For many of the chars a variety of manufacturing procedures were tried in an effort to eliminate or minimize the various problems which arose, such as foaming, lack of mineral dispersion, mineral precipitation, etc. After manufacture, the chars were size classified by repeatedly grounding the oversize material and sieving it to separate the particles which passed through the 105 micron screen but remained on the 90 micron screen. After size-classification the chars were characterized by scanning electron microscopy (SEM) and mercury intrusion porosimetry. The chars were then evaluated based on the following criteria: time required for production, cost of production, ease of mineral matter incorporation, as well as char purity, shape, and pore structure. Table 5.3-7 is an abbreviated summary of the synthetic char evaluations.

TABLE 5.3-7. - Synthetic chars explored

Char Type	Production of 4g of Size-Classified Char		Purity	Mineral Matter Incorporation		Particle Shape and Structure
	Effort	Expense		Atomic	Included	
Sucrose	10 days	Negligible	150 ppm	Yes	Yes	Flat surfaces, sharp edges strictly microporous homogeneous
Sucrose/ Carbon Black	2 days	Negligible	Depends on the carbon black, typically 500 ppm, mostly Na, Ca, Mg, Si	Yes	Yes	Coal-like shape, increased porosity between 0.003 and 0.01 μm , heterogeneous
Sucrose/ Graphite	2 days	Negligible	150 ppm	Yes, but distribution limited		Agglomerate, strictly microporous, heterogeneous
Sucrose/ Decacyclene	10 days	Negligible	150 ppm	Yes	Yes	Flat surfaces, sharp edges, increased porosity between 0.1 and 1.0 μm , heterogeneous
Polymerized Furfuryl Alcohol	20 days	Negligible	Not sure, depends on the furfuryl alcohol	Yes, but content difficult to control		Flat surfaces, sharp edges, strictly microporous homogeneous
Spherocharb	1 hr	\$500	760 ppm, mostly Fe	Yes, but distribution limited	No	Spherical, extremely porous, homogeneous
Reconstructed Coal	1 to 10 days	Negligible	Probability > 1000 ppm significant SiO_2 , Al_2O_3	Yes, but distribution limited		Agglomerate, porosity is that of coal char, structural integrity questionable

For ease of results comparisons, a single type of char was to be used for all vaporization experiments. The char had to be inexpensive, easy to produce in 20g quantities, and incorporation of either included or atomically dispersed minerals had to be accomplished easily. In addition, a shape and pore structure similar to coals was highly desirable. As is apparent from Table 5.3-7, the obvious choice was the sucrose/carbon black char.

The chars for production of submicron ash of controlled composition also had to be inexpensive and easy to produce in 20g quantities; however, incorporation of mineral inclusions was unnecessary, and char shape and pore structure were inconsequential. Char purity, conversely, was much more important in this case. As is shown in Table 5.3-7, the simplest, easiest-to-produce, high purity chars were made from sucrose only. Thus, sucrose chars were used to produce submicron ash of controlled composition.

The sucrose/carbon black was produced by first dissolving 10g of sucrose and suspending 10g of carbon black in approximately 100 ml of distilled water. One half milliliter of isooctylphenoxypolyethoxyethanol (Triton X-100) was also added as a non-ionic surfactant. Minerals that were to be present as inclusions (pyrite, silica, and illite) were suspended in the slurry and those that were to be atomically dispersed were dissolved in the slurry (iron citrate, calcium acetate, and sodium carbonate). The slurry was then alternately sonicated and heated while stirring until thick, at which time the slurry was poured into a charring boat and placed in the pyrolysis furnace. Sonication facilitated carbon black and mineral inclusion dispersion while heating caused the water to evaporate and the slurry to thicken. The slurry was charred twice, first for 1 to 2 hr at 250°C and then at 600°C for 2 hr. Between charrings the char was removed from the furnace and ground. Grinding, which was labor intensive, was accomplished more easily after charring at only 250°C.

The procedure for the production of the sucrose chars, which were to be used to generate submicron ash of controlled composition, was virtually identical to that for the sucrose/carbon black char with the exception that carbon black and the surfactant were not added prior to charring.

The char yield from the sucrose was approximately 20 wt% and that from the carbon black was nearly 100%. Thus, the char resulting from the mixture of sucrose and carbon black was essentially 80 wt% 0.03 μm carbon black particles held together with 20 wt% sucrose char acting as a "glue or binder."

The sucrose/carbon black chars were designed to simulate a simplified coal char. A thorough characterization of the chars (pore size distribution, shape, particle size distribution, inclusion size, and inclusion dispersion) was required for later modeling work.

In order to determine the char pore structure during burnout, a sample of the sucrose/carbon black char was further pyrolyzed for 0.5s at 1650 K in the laminar entrained-flow reactor. The pore size distribution of the sucrose/carbon black synthetic char is shown in Figure 5.3-5 along with pore size distributions from an Upper Freeport bituminous coal char and a North Dakota Beulah lignite char (also generated at 1650 K for

V-441

C-2145

FIGURE 5.3.5. - Scanning electron micrographs and particle size distribution by laser diffraction of the 90 to 106 μm sucrose/50% carbon black char.

0.5s) for comparison. All pore size distributions were determined by mercury porosimetry. The pore size distribution of the sucrose/carbon black char was narrower than that for the coals which is convenient for modeling purposes. The void fraction and specific gravity from mercury porosimetry were 0.53 and 0.94, respectively.

The N₂ BET surface area was 130 m²/g. The shape of the sucrose/carbon black char was surprisingly similar to that of coal and the particle size distribution after size-classification was nearly identical to that of the similarly classified 90 to 106 micron coal samples. Both the coals and the synthetic chars had a mass mean size and standard deviation of approximately 130 and 8 μ m, respectively.

The minerals to be used as inclusions were centrifugally air-classified using a Donaldson Acucut machine to a nominal size of less than 2 μ m. In each case, the range and mass mean particle size obtained by manual image analysis were approximately 1 to 5 and 4 μ m, respectively.

In order to verify that the inclusions were uniformly dispersed throughout the char, samples were cross-sectioned, polished, and examined using the SEM. Four scanning electron micrographs of the sucrose/carbon black char doped with 4 wt% pyrite inclusions is shown in Figure 5.3-6. The inclusions appear to be uniformly distributed in this sample. In previous test chars with larger inclusions, uniform dispersion was questionable; consequently, those chars were not used.

The composition of each of the size classified sucrose/carbon black chars that were used in vaporization experiments was determined by ICPES and appears in Table 5.3-8. The composition of the coal samples also used for vaporization studies have been included in Table 5.3-8 for comparison.

Four sucrose chars were produced for subsequent submicron ash production; their approximate compositions were as follows:

- 10 wt% calcium, atomically dispersed
- 10 wt% iron atomically dispersed
- 5 wt% calcium, atomically dispersed; 5 wt% iron, atomically dispersed
- 5 wt% calcium, atomically dispersed; 5 wt% iron, atomically dispersed, 5 wt% included silica.

These chars were used only to produce an aerosol of controlled composition, not to model vaporization behavior during combustion; therefore, a thorough char characterization was not required. No attempt was made to simulate either the mineral loadings or distributions that exist in coal chars, or the combustion conditions that exist in an industrial boiler. In fact, these chars intentionally have unrealistic mineral contents and were burned with high levels of oxygen, both in order to optimize the quantity of submicron ash produced. The sucrose chars were sieved to between 38 and 105 μ m to facilitate feeding the samples to the laminar, entrained-flow reactor.

V 445

FIGURE 5.3.6. - Scanning electron micrographs of four cross sections of 90 to 106 μm sucrose/carbon black char particles doped with 4 wt%, 1 to 5 μm hydrothermal pyrite particles. The char is outlined and the inclusions, which were identified by EDX microanalysis, are cited in the lower, right-hand micrograph.

5.3.2.2 Experimental Results

5.3.2.2.1 Iron Results

Table 5.3-9 shows the fraction of iron appearing in the submicron ash for two different synthetic chars, two coals, and two pyrite samples. The experiments performed with the synthetic char doped with 4 wt% 1 to 5 μm pyrite were repeated and are shown in columns 1 and 2 of Table 5.3-9. These results are within less than 10% of one another under most conditions. The second type of synthetic char used for iron vaporization was doped with 4 wt% pyrite and 2 wt% atomically dispersed calcium. This synthetic char was burned in order to assess the importance of pyrite-calcium interactions. When comparing

TABLE 5.3-8. - Iron, silicon, and calcium content of the 90 to 106 μm sucrose/carbon black synthetic chars and coals as determined by ICPES

Nominal Composition	Elemental Composition by ICPES (wt% of char)		
	Fe	Si	Ca
4 wt% included SiO_2	-	2.04	-
4 wt% included SiO_2 4 wt% included FeS_2	-	1.71	-
4 wt% included SiO_2 1 wt% Na, atomically dispersed	-	1.79	-
4 wt% included Illite	-	1.04	-
4 wt% included FeS_2	1.15	-	-
4 wt% included FeS_2 2 wt% Ca, atomically dispersed	1.33	-	1.31
2 wt% Ca, atomically dispersed	-	-	1.24
Kentucky #9 Bituminous coal	1.44	2.33	0.18
North Dakota Beulah Lignite	1.22	1.17	1.15

the results of the synthetic char doped with pyrite and calcium (column 3) to the results from chars doped only with pyrite (columns 1 and 2), little difference exists under all conditions greater than 0% oxygen. However, at 0% oxygen the data has the largest percentage error, indicating that this difference may not be significant. Thus, under oxidizing conditions the calcium had a negligible effect on the fraction of the initial iron found in the submicron ash. A much larger fraction of the iron from the synthetic chars (columns 1-3) appears in the submicron ash than does from the coals (columns 4 and 5). This is presumably due to a difference in inclusion sizes. The computer-controlled scanning electron microscopy data given in Tables 5.3-10 and 5.3-11 showed that the pyrite inclusions in the raw Phase I Kentucky #9 bituminous coal (utility grind sample; 70% through 200 mesh screen) had a very broad size distribution with 7% (on a cross-sectional area basis) below $2.5 \mu\text{m}$ and only 21% greater than $40 \mu\text{m}$, while the pyrite inclusions in the raw North Dakota Beulah lignite had only 2% below $5 \mu\text{m}$ and 56% greater than $40 \mu\text{m}$. Assuming vaporization is the ash formation mechanism, and assuming that the vaporization reaction is not at equilibrium throughout the char, one expects that for a given mass fraction of pyrite in the char, smaller inclusions will produce more vapor. This qualitatively explains the difference between the two coals as well as the difference between the coals and the synthetic chars. The extraneous pyrite (columns 6 and 7) has the lowest fraction of the initial iron appearing in the submicron ash. This is presumably because the extraneous pyrite consists of very large particles and/or because the extraneous pyrite does not experience the reducing atmosphere of the char interior. Consequently, the contribution to the iron in the submicron ash from extraneous pyrite is negligible.

TABLE 5.3-9. - Fraction of the iron found in the submicron ash

Fraction of the Iron in the Submicron Ash							
Oxygen Conc. (%)	Suc/CB Char 4% Pyrite 90 to 105 μm	Suc/CB Char 4% Pyrite 90 to 105 μm	Suc/CB Char 4% Pyrite, 2% Ca, 90 to 105 μm	Ky #9 Bit. Coal 90 to 105 μm	ND Beulah Lignite 90 to 105 μm	Ky #9 Pyrite 38 to 105 μm	ND Beulah Pyrite 38 to 105 μm
0	0.008	0.018	0.002			0.0003	0.0001
10		0.072	0.062			0.0004	0.0009
20	0.372	0.358	0.361	0.027	0.038	0.0033	0.0084
30	0.572	0.520	0.572			0.0253	0.0334
35				0.082	0.097		
50	0.539	0.563	0.609	0.120	0.104	0.0402	0.0592
65				0.128	0.108		
80	0.608	0.587	0.583	0.147	0.106	0.0677	0.0864
Gas temperature 1650K							

TABLE 5.3-10. - Beulah lignite mineral size distributions as determined by computer-controlled scanning electron microscopy

Mineral	Wt% in Coal	Wt% in Mineral Matter	Size Distribution in Wt%					
			<2.5 μm	2.5 to 5 μm	5 to 10 μm	10 to 20 μm	20 to 40 μm	> 40 μm
Quartz	1.2	12	11	11	17	23	19	18
Kaolinite	3.1	31	42	7	9	13	12	17
Illite Mix.	0.1	1	-	-	-	-	-	-
Silicates	1.4	14	73	6	7	7	7	0
Pyrite	2.6	26	1	1	3	12	26	56
Jarosite	0.3	3	-	-	-	-	-	-
Fe ²⁺ Sulfates	0.2	2	-	-	-	-	-	-
Miscellaneous	1.1	11	-	-	-	-	-	-
All Minerals	10.0	100	27	7	8	13	16	30
Data from Boni et al., 1990								

TABLE 5.3-11. - Kentucky #9 bituminous coal (Phase I, utility grind sample) mineral size distributions as determined by computer-controlled scanning electron microscopy

Mineral	Wt% in Coal	Wt% in Mineral Matter	Size Distribution in Wt%					
			<2.5 μm	2.5 to 5 μm	5 to 10 μm	10 to 20 μm	20 to 40 μm	>40 μm
Quartz	1.9	12	13	31	25	24	7	1
Kaolinite	0.9	6	20	35	24	14	6	1
Illite Mix.	3.6	23	26	24	17	14	8	11
Silicates	5.4	35	19	19	20	11	10	21
Pyrite	2.5	16	7	18	18	19	18	21
Jarosite	0.3	-	-	-	-	-	-	-
Fe ²⁺ Sulfates	0.2	-	-	-	-	-	-	-
Miscellaneous	1.1	7	-	-	-	-	-	-
All Minerals	15.4	100	24	21	17	15	11	12
Data from Boni et al., 1990								

5.3.2.2.2 Silicon Results

Table 5.3.12 shows the fraction of silicon appearing in the submicron ash for four different synthetic chars and two coals. Unfortunately the silicon in the submicron ash from most of the chars was indistinguishable from the background for zero to 20% oxygen. The synthetic char doped with only 4 wt% silica (column 1) is a base case to which the other synthetic chars can be compared. Column 2 of Table 5.3-12 shows the results for the char doped with 4 wt% silica and 4 wt% pyrite. The pyrite was added as a source of sulfur to investigate the importance of SiS as a vaporizing species. The presence of sulfur increased the silica vaporization under all detectable conditions, especially 0% oxygen. Columns 3 and 4 of Table 5.3-12 show the results for synthetic chars doped with 4 wt% silica with 1 wt% sodium and another with 4 wt% illite ($K_{1-1.5}Al_4Si_{7-6.5}Al_{1-1.5}O_{20}(OH)_4$). Both of these chars show reduced silica vaporization when compared to the base case at lower oxygen levels. At higher oxygen levels the vaporization rates increase rapidly, reaching comparable vaporization rates at the highest oxygen levels. These results indicate a depression of silica activity at lower oxygen levels and stronger vaporization temperature dependence for the silicate mixtures. A much smaller fraction of the silica from the coals appeared in the submicron ash. This is presumably due to the larger silicate particles present in the coals and/or a lower activity of the silica present in the coals. A lower silica activity in the coal could be due to either the silica being present as aluminosilicates or reaction of the silicates with alkaline and alkaline earth species.

5.3.2.2.3 Calcium Results

Two synthetic chars were used to investigate calcium behavior. The results generated using those synthetic chars as well as the results from two coals are shown in Table 5.3-13. The synthetic char doped with 2 wt% finely dispersed calcium (column 1) shows a dramatic increase in the mass of calcium in the submicron ash between 20 and 30% oxygen. The synthetic char with 2 wt% calcium and 4 wt% pyrite (column 2) shows slightly lower fractions of calcium in the submicron ash, possibly due to the formation of calcium sulfide. The Kentucky #9 bituminous coal shows no significant vaporization, presumably because the calcium is present as discrete carbonate inclusions rather than atomically dispersed. The North Dakota Beulah lignite behaves in a similar manner as the synthetic chars. This similarity is easily rationalized because the calcium in Beulah lignite is also atomically dispersed.

5.3.2.2.4 Results Summary

1. At the conditions most closely resembling those in a utility boiler (1650 K gas temperature and 20% oxygen), the submicron ash consisted of primary particles between 0.01 and 0.06 μm and had a stratified composition. Chemical analysis by scanning transmission electron microscopy did not detect any iron or silica rich particles. Furthermore, as the oxygen level was increased, both the size and number of primary particles increased. These results support the conclusion that vaporization was the mechanism of submicron ash formation. In fact, no evidence for any other submicron ash formation mechanism (such as char fragmentation) was found in the experiments with size-classified coals conducted in this study.

TABLE 5.3-12 - Fraction of the silicon found in the submicron ash

Oxygen Conc. (%)	Fraction of the Silicon in the Submicron Ash					
	Suc/CB Char 4% Silica 90 to 105 μm	Suc/CB Char 4% Silica 4% Pyrite 90 to 105 μm	Suc/CB Char 4% Silica 2% Na 90 to 105 μm	Suc/CB Char 4% Illite 90 to 105 μm	Ky #9 Bituminous Coal 90 to 105 μm	ND Beulah Lignite 90 to 105 μm
0	<0.004	0.017	<0.004		<0.004	<0.004
10	<0.004	<0.004	<0.004		<0.004	<0.004
20	0.005	0.012	<0.004	<0.004	<0.004	<0.004
30	0.028	0.032	0.006	0.006	<0.004	<0.004
50	0.074	0.172	0.036	0.096	0.015	0.008
80	0.096	0.149	0.110	0.107	0.033	0.020
Gas temperature 1650 K						

TABLE 5.3-13. - Fraction of the calcium found in the submicron ash

Oxygen Conc. (%)	Fraction of the calcium in the submicron ash			
	Suc/CB Char 2% Ca 90 to 105 μm	Suc/CB Char 4% Pyrite 2% Ca 90 to 105 μm	Ky #9 Bituminous Coal 90 to 105 μm	ND Beulah Lignite 90 to 105 μm
0	<0.01	<0.01		
10	<0.01	<0.01		
20	0.021	<0.01		0.016
30	0.282	0.100		
35				0.107
50	0.695	0.594		0.220
65				0.277
80	0.711	0.617	0.026	0.352
Gas temperature 1650 K				

2. Intrinsic pyrite is responsible for iron vaporization. Iron vaporization is a strong function of pyrite inclusion size. No evidence was found for important mineral matter interactions which limit vaporization.
3. Silicon vaporization is influenced both by inclusion size and mineral interactions. Sulfur enhances silica vaporization, sodium and potassium suppress it. Aluminosilicates have a depressed silicon vaporization rate.
4. Calcium vaporization is only significant from atomically dispersed calcium and is slightly depressed by the presence of sulfur.

5.3.2.3 Vaporization Model

As concluded in the previous Subsection 5.3.2.2.4, the experimental results show no indication of any submicron ash formation mechanisms other than vaporization. Furthermore, microscopy results from the following chapter on submicron ash characterization also strongly support a vaporization/condensation mechanism with no evidence for any other submicron ash formation mechanisms. Thus, a modeling effort was undertaken in order to (1) determine if a vaporization mechanism could quantitatively explain the results presented in Subsection 5.3.2.2 and (2) to differentiate between different vaporization mechanisms. This section describes the model. The following Subsection, 5.3.2.4, uses the model to facilitate further interpretation of the experimental results which were presented in Subsection 5.3.2.2.

5.3.2.3.1 Internal Transport and Reaction

This model assumes the following:

1. The submicron ash is the result of vaporization only and it contains all the vaporized material.
2. As with the combustion model, the char is assumed to burn in pseudo-steady state in a stagnant gas of infinite extent.
3. Vaporization is limited by the diffusion of the volatile species from the inclusion surface to the char surface.
4. Diffusion through the pore matrix is well represented by a single effective diffusivity.
5. The inclusions are much smaller than the char particle.
6. There is only a single type and size of inclusion present in the char and it is uniformly distributed throughout the char.
7. Vaporization is driven by the gas phase concentration of the volatile species at the inclusion surface.
8. The volatile species can be modeled as diffusing from the inclusion surface to a mean concentration in the char. The mean concentration in the char is a function of radius (mean field approximation).

The model is illustrated in Figure 5.3-7. This model is similar in many respects to that of Quann and Sarofim (1982).

A shell balance may be written within the char particle.

$$j_M|_r 4\pi r^2 - j_M|_{r+\Delta r} 4\pi (r+\Delta r)^2 = -R_{vap} 4\pi r^2 \Delta r \quad (5.46)$$

where:

M	=	vaporizing species
X_M	=	mean field mole fraction M
r	=	radial distance from char center
R_{vap}	=	molar rate of vaporization per unit char volume
j_M	=	molar flux of species M .

Where:

X_m = mean field mole fraction metal vapor species

X_m^i = mole fraction metal vapor species at inclusion surface

X_m^s = mole fraction metal vapor species at char surface

C-1898

FIGURE 5.3-7. - Vaporization model.

Dividing Eq. (5.46) by the shell volume, $4\pi r^2 \Delta r$, and taking the limit as $\Delta r \rightarrow 0$, we obtain the following differential equation.

$$\frac{1}{r^2} \frac{d(j_M r^2)}{dr} = R_{vap} \quad (5.47)$$

Within the char the pore diameter ($\sim 0.1 \mu\text{m}$) is much less than the mean free path of the gas ($\sim 1 \mu\text{m}$); therefore, Stefan flow is irrelevant and the flux should be well described by Fick's law of diffusion.

$$j_M = -cD_M^e \left(\frac{dX_M}{dr} \right) \quad (5.48)$$

where

$$\begin{aligned} D_M^e &= \text{effective diffusivity of vapor species M in the char} \\ c &= \text{gas concentration in the char.} \end{aligned}$$

Given the pore size of $0.1 \mu\text{m}$ for the synthetic char, the effective diffusivity is simply the Knudsen diffusivity multiplied by the void fraction and divided by the char tortuosity (see (5.22) and related discussion in Subsection 5.3.1.2.2.2).

Combining Eqs. (5.47) and (5.48), we have the following differential equation:

$$\left(\frac{d^2 X_M}{dr^2} \right) + \frac{2}{r} \frac{dX_M}{dr} = \frac{-R_{\text{vap}}}{cD_M^e} \quad (5.49)$$

which must be solved subject to the following boundary conditions:

$$\frac{dX_M}{dr} = 0 \quad \text{at } r=0, \text{ and } X_M = X_M^s \text{ at } r=r_p$$

where

$$\begin{aligned} X_M^s &= \text{mole fraction species M at char surface} \\ r_p &= \text{char particle radius.} \end{aligned}$$

In order to solve Eq. (5.49), an expression for R_{vap} is required.

The molar rate of vaporization per unit char volume may be written as follows:

$$\begin{aligned} R_{\text{vap}} &= I_v J_M^i = (I_p/V_p) J_M^i = \left(\frac{V_p \rho_p f_i (1/\rho_i)}{V_i} \right) \frac{1}{V_p} J_M^i \\ &= \frac{\rho_i f_i (1/\rho_i) J_M^i}{(4/3)\pi r_i^3} \end{aligned} \quad (5.50)$$

where:

J_M^i	=	molar rate of vaporization for a single inclusion
I_v	=	inclusions/unit of char volume
I_p	=	inclusions/char particle
V_p	=	volume of a char particle
ρ_p	=	char density
ρ_i	=	inclusion density
f_i	=	mass fraction of char that is inclusion
V_i	=	volume of an inclusion
r_i	=	inclusion radius.

In order to determine an expression for the molar rate of vaporization for a single inclusion, consider a single inclusion with a concentration X_M^i at the inclusion surface in a mean field concentration of X_M . Diffusion from the inclusion to the mean field concentration is given by the following equation:

$$J_M^i = cD_M^* 4\pi r_i (X_M^i - X_M) \quad (5.51)$$

The following expression for R_{vap} is derived by substituting Eq. (5.51) into (5.52):

$$R_{vap} = \frac{3(\rho_p/\rho_i) f_i cD_M^* (X_M^i - X_M)}{r_i^2} \quad (5.52)$$

which can then be substituted into Eq. (5.49) to give:

$$\frac{d^2 X_M}{dr^2} + \frac{2}{r} \frac{dX_M}{dr} + \frac{\phi^2 (X_M^i - X_M)}{r_p^2} = 0 \quad (5.53)$$

where

$$\phi = \left[3 \left(\frac{\rho_p}{\rho_i} \right) f_i \right]^{1/2} \frac{r_p}{r_i} \quad (5.54)$$

and

r_p = char radius .

The variable ϕ can be thought of as a modified Thiele modulus which represents the extent of mineral matter dispersion within the char. Equation (5.53) can be solved with boundary conditions given earlier to give the mean field concentration within the char as a function of X_M^i , X_M^s , ϕ , and r/r_p .

$$X_M = X_M^i \left[1 - \left(\frac{X_M^s}{X_M^i} \right) \left(\frac{r_p \sinh \left(\frac{\phi r}{r_i} \right)}{r \sinh \phi} \right) \right] \quad *p899Y \quad (5.55)$$

The total flow of vapor species away from the char (J_M) can be derived by taking the derivative of Eq. (5.55) and substituting it into Eq. (5.48) to give the vapor flux $= j_M = f(r)$. The resulting flux equation can then be evaluated at $r = r_p$ and multiplied by the external char surface area to give the following equation for the total flow of vapor species M out of the particle:

$$J_M = 4\pi r_p c D_M^s (X_M^i - X_M^s) \left[\frac{\phi}{\tanh \phi} - 1 \right] \quad (5.56)$$

This is the equation we need; however, it is a function of X_M^s , the mole fraction of the vapor species at the char surface, which is a function of both internal and external transport.

5.3.2.3.2 External Transport

By writing a shell balance in the boundary layer surrounding the burning char particle, the following expression can be derived:

$$\frac{1}{r^2} \frac{d(j_n r^2)}{dr} = R_{\text{oxid}} = k_{\text{oxid}} X_M^n X_{O_2}^m \quad (5.57)$$

where:

- R_{oxid} = molar rate of gas phase oxidation of vapor species M per unit volume gas
- k_{oxid} = rate constant for the oxidation reaction
- n, m = order of reaction in the vapor species M and O_2 , respectively.

The molar flux of the vapor species M, j_M , may be written as the sum of the diffusive flux and the bulk flux due to Stefan-flow as shown in Eq. (5.58):

$$j_M = -cD_M \frac{dx_M}{dr} + X_M \sum_{n=1}^m j_n \quad (5.58)$$

where:

c = gas concentration in the boundary layer
 D_M = diffusivity of vapor species M in the boundary layer.

In Subsection 4.2.2.3 the sum of the fluxes of the major species (O_2 , CO, CO_2) in the boundary layer of the burning char was shown to be as follows:

$$\sum_{n=1}^m j_n = j_{O_2} \left(1 - \frac{1}{\psi}\right) \quad (5.26)$$

where ψ = moles O_2 consumed/mole C.

By combining Eqs. (5.57), (5.58), and (5.26), the following general differential equation can be derived to describe external transport and reaction of vapor species M in the boundary surrounding the char particle:

$$-\frac{1}{r^2} \frac{d}{dr} \left[-cD_M r^2 \frac{dx_M}{dr} + X_M \left(\frac{J_{O_2}}{4\pi} \right) \left(1 - \frac{1}{\psi}\right) \right] = k_{oxid} X_M^n X_{O_2}^m \quad (5.59)$$

where J_{O_2} = molar flow of O_2 away from the particle.

One notes that k_{oxid} is a function of temperature, and both temperature and mole fraction O_2 are strong functions of r in the boundary layer. Therefore, in order to solve this equation exactly, the appropriate temperature and oxygen concentration profiles would have to be known. Determination of these profiles is not simple. Thus, instead of attempting to solve this equation exactly, two limiting cases were solved: (1) $R_{oxid} = 0$, oxidation is slow and occurs to a negligible extent within the boundary layer and (2) $R_{oxid} = R_{oxid(max)}$, the reaction rate based on the maximum temperature (char temperature) and maximum O_2 (concentration in the bulk gas) possible in the boundary layer. These two cases will put bounds on the actual solution.

Case 1, $R_{\text{oxid}} = 0$ - Given no significant reaction occurs in the boundary layer, the total flow of vapor species M is not a function of radial position

$$j_M 4\pi r^2 = J_M = \text{constant} \quad . \quad (5.60)$$

Combining Eqs. (5.58), (5.26), and (5.60), the following equation may be written:

$$\frac{J_M}{4\pi r^2} = -cD_M \frac{dX_M}{dr} + X_M \frac{J_{O_2}}{4\pi r^2} \left(1 - \frac{1}{\psi}\right) \quad . \quad (5.61)$$

Equation (5.61) may be rearranged and integrated using the following boundary conditions:

$$\text{at } r = r_p \quad X_M = X_M^s$$

$$\text{at } r = \infty \quad X_M = 0$$

to give the following expression for the total molar flow of vapor species M away from the particle:

$$J_M = \frac{-X_M^s J_{O_2} \left(\frac{1}{\psi} - 1\right)}{1 - \exp \left[\frac{J_{O_2} \left(\frac{1}{\psi} - 1\right)}{cD_M 4\pi r_p} \right]} \quad (5.62)$$

where:

$$\overline{cD_M} = cD_M \text{ evaluated at } T = (T_p + T_g)/2$$

$$T_p = \text{particle temperature}$$

$$T_g = \text{bulk gas temperature.}$$

As shown in Subsection 5.3.1.2.2.3, the product of the gas concentration and the diffusivity varies by only a factor of 1.5 across the boundary layer under the most extreme conditions; therefore, a simple median value is an accurate approximation.

Case 2, $R_{\text{oxid}} = R_{\text{oxid}}(\text{max})$ - Given that the contribution by Stefan-flow is small, it is not considered in this case. Equation (5.59) can be rewritten without Stefan-flow and with the maximum reaction rate as follows:

$$\frac{1}{r^2} \frac{d}{dr} \left[cD_M r^2 \frac{dX_M}{dr} \right] = k_{\text{oxid}}(\text{max}) X_M X_{O_2}^b \quad (5.63)$$

where:

$$\begin{aligned} k_{\text{oxid}}(\text{max}) &= k_{\text{oxid}} \text{ evaluated at the char temperature} \\ X_{O_2}^b &= O_2 \text{ mole fraction in the bulk gas.} \end{aligned}$$

Defining the variables:

$$\begin{aligned} \alpha &= \frac{k_{\text{oxid}}(\text{max}) X_{O_2}^b}{\overline{cD_M}} \\ \gamma &= rX_M \end{aligned}$$

where $\overline{cD_M} = cD_M$ evaluated at $T_m = (T_p + T_g)/2$ (see discussion following Eq. (5.62)).

Equation (5.63) can be rewritten as follows:

$$\frac{d^2 \gamma}{dr^2} - \alpha \gamma = 0 \quad (5.64)$$

The general solution to Equation (5.64) is

$$\gamma = rX_M = C_1 \cosh(r\sqrt{\alpha}) + C_2 \sinh(r\sqrt{\alpha}) \quad (5.65)$$

where $c_1, c_2 = \text{constants}$.

The boundary conditions of choice to determine c_1 and c_2 are:

$$\begin{aligned} \text{b.c. 1) at } r = r_p & \quad X_M = X_M^s \\ \text{b.c. 2) at } r = \infty & \quad X_M = 0 \end{aligned}$$

or, given that X_M approaches 0 faster than r approaches infinity, a third boundary condition may be written

$$\text{b.c. 3) as } r \rightarrow \infty, rX_M \rightarrow 0.$$

Constants c_1 and c_2 can be determined using boundary conditions 1 and 3

$$c_1 = -c_2 = \frac{X_M^\infty r_p}{\exp(-r_p \sqrt{\alpha})} \quad (5.66)$$

The flux of vapor species M away from the char can be derived by taking the derivative of the concentration profile (Eq. (5.21)) and substituting it into Eq. (5.58). Neglecting Stefan-flow in Eq. (5.58), this gives the following equation:

$$j_M = cD_M \left[\frac{c_1 \sqrt{\alpha}}{r} + \frac{c_1}{r^2} \right] \exp(-r \sqrt{\alpha}) \quad (5.67)$$

The total flow of vapor species M away from the surface is given by evaluating the flux at $r = r_p$ and multiplying that flux by the external char surface area

$$J_M = j_M |_{r_p} 4\pi r_p^2 = 4\pi r_p^2 cD_M |_{T_p} \left[\frac{c_1 \sqrt{\alpha}}{r_p} + \frac{c_1}{r_p^2} \right] \exp(-r_p \sqrt{\alpha}) \quad (5.68)$$

(noting that in this case cD_M is evaluated at $r = r_p$ where $T = T_p$) which when combined with Eq. (5.66) yields the following equation for the total molar flow of species M away from the char surface at $r = r_p$:

$$J_M = 4\pi r_p^2 cD_M |_{T_p} X_M^\infty \left[\sqrt{\alpha} + \frac{1}{r_p} \right] \quad (5.69)$$

5.3.2.3.3 Overall Model

Given we have equations describing the total flux of vapor species M away from the char surface derived from both internal and external transport we can combine them to solve for the unknown mole fraction vapor species at the char surface, X_M^∞ .

Case 1, $R_{\text{oxid}} = 0$

$$\begin{aligned}
J_M (\text{internal}) &= 4\pi r_p cD_M^* (X_M^i - X_M^s) \left[\frac{\phi}{\tanh\phi} - 1 \right] \\
&= \frac{-X_M^s J_{O_2} \left(\frac{1}{\psi} - 1 \right)}{1 - \exp \left[\frac{J_{O_2} \left(\frac{1}{\psi} - 1 \right)}{cD_M^* 4\pi r_p} \right]} = J_M (\text{external}) \quad (5.70)
\end{aligned}$$

$$\begin{aligned}
X_M^s &= \frac{4\pi r_p cD_M^* X_M^i \left[\frac{\phi}{\tanh\phi} - 1 \right]}{\frac{J_{O_2} \left(\frac{1}{\psi} - 1 \right)}{1 - \exp \left[\frac{J_{O_2} \left(\frac{1}{\psi} - 1 \right)}{cD_M^* 4\pi r_p} \right]} + 4\pi r_p cD_M^* \left[\frac{\phi}{\tanh\phi} - 1 \right]} \quad (5.71)
\end{aligned}$$

Case 2, $R_{\text{oxid}} = R_{\text{oxid}}(\text{max})$

$$\begin{aligned}
J_M (\text{internal}) &= 4\pi r_p cD_M^* (X_M^i - X_M^s) \left[\frac{\phi}{\tanh\phi} - 1 \right] \quad (5.72) \\
&= 4\pi r_p^2 cD_M |_{T_p} X_M^s (\sqrt{\alpha} + 1/r_p) = J_M (\text{external})
\end{aligned}$$

$$X_M^s = \frac{cD_M^* X_M^i \left[\frac{\phi}{\tanh\phi} - 1 \right]}{r_p cD_M |_{T_p} (\sqrt{\alpha} + 1/r_p) + cD_M^* \left[\frac{\phi}{\tanh\phi} - 1 \right]} \quad (5.73)$$

For both case 1 and 2 we have $X_M^s = f(X_M^i, \phi, r_p, J_{O_2}, T_p)$ (Eqs. (5.71) and (5.73))

and $J_M = f(X_M^s, X_M^i, \phi, r_p, T_p)$ (Eq. (5.56)). For a given particle size, r_p , the modified Thiele modulus, ϕ , can be calculated with Eq. (5.54). From Subsection 5.3.1 we have J_{O_2} and T_p as a function of r_p for a given combustion environment. Thus, we can calculate $J_M = f(X_M^i, r_p)$. Furthermore, we can use the burning rates calculated as a function of r_p in Subsection 5.3.1 to numerically integrate the molar vaporization rate, J_M ,

during burnout to give the total moles of species M vaporized from a single char particle, N_M

$$N_M = \int_0^{t_b} J_M dt \quad (5.74)$$

where t_b = burnout time.

The total moles of species M vaporized during burnout can easily be related to the fraction of M vaporized, which is the quantity reported as a function O_2 concentration in Subsection 5.1.

In summary, if we know X_M^i we can use the combustion model of Subsection 5.3.1 and the vaporization model of this section to model the results of the previous Subsection 5.3.2.2.

5.3.2.4 Results Interpretation

5.3.2.4.1 General Approach

The question unanswered at the end of Subsection 5.2 is "How to choose the mole fraction vapor species M at the inclusion surface (X_M^i)?" A vaporization reaction was assumed to be in equilibrium at the inclusion surface. This begs the next question: what is the appropriate vaporization reaction? In order to answer this question one must know the following:

1. What is the condensed phase?
2. Is equilibrium constrained? If so, how is it constrained? (i.e., is equilibrium with C achieved?, is equilibrium with CO achieved?)
3. What is the dominant gas species?

For the chars containing pyrite or silica inclusions there are several possible answers to each of the above three questions. For example, with silica inclusions there are two possible condensed phases (SiO_2 and SiC), two possible equilibrium constraints, and four possible vapor species (SiO_2 , SiO, Si, and SiC).

Modeling with each possible vaporization reaction and then comparing it to the data was too tedious. Instead, the experimental data was transformed into a mean vapor pressure of species M at the char surface, $\overline{X_M^s}$. A simple order of magnitude analysis of Eqs. (5.71)

and (5.73) assuming that the mineral was present as discrete $4 \mu\text{m}$ inclusions shows that x_M^i must be approximately 10 to 100 times greater than $\overline{x_M^s}$ for case 1, and 100 to 1000 times greater than $\overline{x_M^s}$ for case 2. Assuming the mineral was present as an atomically dispersed species, then $x_M^i \approx \overline{x_M^s}$ for case 1, and x_M^i must be approximately 10 times greater than $\overline{x_M^s}$ for case 2. Given these differences, the mean vapor pressure at the char surface, $\overline{x_M^s}$, was compared directly to the vapor pressure at the inclusion surface, x_M^i , produced from the different possible vaporization reactions. This comparison allowed for the rapid elimination of those vaporization reactions which were unreasonable.

Thus, the first step in results interpretation was the conversion of the data (fraction of species M vaporized, f_{Mv}) to a mean vapor pressure at the char surface. In Subsection 5.3.2.3.2, Eqs. (5.18) and (5.25) were derived from external transport for the flow of species M away from a char particle. These equations present the flow of species M as a function of the mole fraction species M at the char surface, char size, char temperature, and the combustion rate:

$$J_M = f(x_M^s, r_p, T_p, J_{O_2}) \quad (5.75)$$

Equations (5.62) and (5.69) can now be integrated numerically using the discretized combustion data generated in Subsection 5.3.1 (r_p , T_p , and $J_{O_2} = f(t_b)$) assuming x_M^s is constant to give

$$N_M = f(\overline{x_M^s} \text{ and combustion conditions}) \quad (5.76)$$

where:

N_M = moles M vaporized during combustion of a single char particle

$\overline{x_M^s}$ = mean mole fraction species M at the char surface during burnout.

The experimental data, f_{Mv} , was used to calculate N_M with the following equation:

$$N_M = \frac{\text{moles M vaporized}}{\text{char particle}} = \frac{(4/3) \pi (r_p^0)^3 \rho_p f_{M_i} f_{M_v}}{MW_M} \quad (5.77)$$

where:

$$\begin{aligned} r_p^0 &= \text{initial char particle diameter} \\ \rho_p &= \text{density of the char particle} \\ f_{M_i} &= \text{mass fraction of the char that is species M} \\ f_{M_v} &= \text{mass fraction of species M that vaporizes} \\ MW_M &= \text{molecular weight of species M.} \end{aligned}$$

For a given experiment, N_M and the combustion conditions were known, and $\bar{X}_M^s$ was calculated. Because the integration was numerical, the calculation was iterative. A value for $\bar{X}_M^s$ was chosen, the integration was performed, the calculated N_M was compared to the N_M from the data and, if necessary, a new value of $\bar{X}_M^s$ was chosen and the process was repeated. One should note that this produced a mean mole fraction species M at the char surface which was calculated from experimental data and was weighted with the fraction vaporized, not time.

The second step in the results interpretation was the calculation of the equilibrium mole fraction of species M at the inclusion surface for the different possible vaporization reactions. In many cases the vaporization reaction under consideration was of the following form:

The equilibrium constant for this reaction is given by the following equation:

$$\begin{aligned} K_{5.6} &= \exp \left(-\Delta G_{\text{rxn 5.6}}^0 / RT_P \right) \\ &= \frac{(P_{CO_2}^i / P_T) (P_M^i / P_T)}{a_{MO} (P_{CO}^i / P_T)} = \frac{X_{CO_2}^i X_M^i}{a_{MO} X_{CO}^i} \quad (5.78) \end{aligned}$$

where:

T_p	=	particle temperature
P_T	=	total pressure
R	=	ideal gas constant
P_M^i	=	partial pressure of species M at the inclusion surface
a_{MO}	=	activity of MO
$\Delta G_{rxn\ 5.6}^o$	=	change in the Gibbs free energy due to reaction 5.1 given all reactants and products are in their standard states.

Depending on the vaporization reaction under consideration, additional assumptions were required in order to calculate X_M^i . For example, for the above reaction the following assumptions were made:

1. $a_{MO} = 1$, This assumption is not wholly unjustified given that a 20% error in the activity is acceptable.
2. $X_{CO_2} = X_M$, This assumption is justified if (a) the Boudouard reaction can be neglected, (b) CO_2 and M have similar diffusivities, and (c) the inclusion of interest is the only source of CO_2 and M.

Given these assumptions, Eq. (5.78) can be simplified

$$X_M^i = \sqrt{K_{5.6} X_{CO}^i} \quad (5.79)$$

In order to calculate X_M^i , the equilibrium constant for the vaporization reaction and the mole fraction CO at the inclusion surface were required. The equilibrium constant was calculated using the first part of Eq. (5.78) with the particle temperatures from Subsection 5.3.1 and the free energy data from the JANAF tables. The mole fraction CO at the inclusion surface was calculated assuming the following:

1. $X_{CO}^i = X_{CO}^s$, This is justified given there are no significant sinks or sources of CO within the char.
2. Carbon monoxide oxidation in the boundary layer occurs entirely at the char surface, This is not a bad assumption given that the extent of CO oxidation was estimated to be less than 15% (see Subsection 5.3.1) under all combustion conditions considered.

Given these assumptions, the flow of CO in the boundary layer is given by the following equation:

$$J_{CO} = 4\pi r^2 j_{CO} = 4\pi r^2 \left[-cD_{CO} \frac{dx_{CO}}{dr} + x_{CO} \sum_{n=1}^m j_n \right] = \text{constant} \quad (5.80)$$

$$\begin{aligned} J_{CO} &= \text{molar flow of CO} \\ j_n &= \text{molar flux of species } n \\ D_{CO} &= \text{diffusivity of CO in the boundary layer.} \end{aligned}$$

The total flux of major species (CO, O₂, CO₂) may be rewritten in terms of the CO flux (see Subsection 5.3.1.2.2.3):

$$\sum_{n=1}^m j_n = j_{CO}/2 \quad (5.81)$$

The following equation was derived by substituting Eq. (5.81) into Eq. (5.80), rearranging, and integrating between the char surface ($r = r_p$, $x_{CO} = x_{CO}^s$) and infinity ($r = \infty$, $x_{CO} \approx 0$).

$$J_{CO} = -\overline{cD_{CO}} 8\pi r_p^2 \ln \left(1 - \frac{x_{CO}^s}{2} \right) \quad (5.82)$$

where $\overline{cD_{CO}}$ is cD_{CO} evaluated at $T = (T_p + T_g)/2$, (see Subsection 5.3.1.2.2.3).

Equation (5.82) may be rearranged to yield:

$$x_{CO}^s = x_{CO}^i = 2 - 2 \exp \left(\frac{-J_{CO}}{\overline{cD_{CO}} 8\pi r_p^2} \right) \quad (5.83)$$

The molar flow of CO, J_{CO} , is related to the combustion rate, J_{COx}

$$J_{CO} = 2(1-\psi) J_{COx} \quad (5.84)$$

where: ψ = moles O_2 consumed/mole C and J_{CO_x} and ψ are reported as a function of combustion conditions in Subsection 5.3.1.

This completes the analysis required to compare the mole fraction of species M at the char surface calculated from the data ($\overline{X}_M^g$) to the equilibrium mole fraction M at the inclusion surface due to the different possible vaporization reactions (X_M^i). Once this comparison was made and the feasible vaporization reactions had been identified, the feasible vaporization reactions could be input into the vaporization model of Subsection 5.3.2.3 and $\overline{X}_M^g$ calculated from the model for comparison with that calculated from the data.

In summary, the method of approach for results interpretation had four steps:

1. Convert vaporization data (f_{Mv}) to $\overline{X}_M^g$ (Eqs. (5.62), (5.69), (5.76), and (5.77))
2. Compare $\overline{X}_M^g$ from data to all possible values of X_M^i to identify feasible vaporization reactions.
3. Use feasible vaporization reactions as input to vaporization (Eqs. (5.71) and (5.73)).
4. Compare $\overline{X}_M^g$ from the data and model.

5.3.2.4.2 Calcium

The results that are considered here are those shown in Table 5.3-12 which were produced from a sucrose/carbon black char doped with 2 wt% calcium. The char is described in detail in Subsection 5.3.2.1. However, it is worth noting here that the calcium was introduced as calcium acetate which was dissolved in the sucrose/carbon black solution before charring. The char was pyrolyzed for approximately 2 hr at between 900 and 1000 K. Previous studies on the form of finely dispersed calcium (Radovic et al., 1983 and Huggins et al., 1988) in chars show that the finely dispersed calcium is transformed into discrete inclusions during extended pyrolysis. Scanning electron microscopy with X-ray microanalysis of the calcium doped char after pyrolysis revealed no calcium inclusions greater than one micron. Unfortunately, calcium inclusions less than 1 μm were below the detection limit. Thus, the final form of the calcium in the char was unknown. The data presented in the first column of Table 5.3-12 were transformed to mole fraction (which is equal to the partial pressure, given the total pressure in all experiments was 1 atm) calcium at the char surface using Eqs. (5.62), (5.69), (5.76), and (5.77) and are shown in Figure 5.3-8. The data are reported twice in Figure 5.3-8. The upper set of data assumes no oxidation of calcium vapor in the char boundary layer (case 1, Eq. (5.62)), and the lower set assumes the maximum oxidation rate of calcium in the boundary layer (case 2,

C-1697

FIGURE 5.3.8 - Calculated average calcium vapor pressure at the char surface during burnout compared to several equilibrium calcium vapor pressure curves.

Eq. (5.69)). The gas-phase oxidation kinetics were estimated from kinetic theory. The maximum rate was estimated using the particle temperature and the bulk O_2 concentration. The rate-limiting step was assumed to be

The O atom formed in this reaction is assumed to react predominantly with species other than calcium vapor. This is supported by the work of Markstein (1963) who found this to be the rate-limiting step for homogeneous magnesium vapor oxidation under similar conditions.

There are two conceivable condensed phases for the calcium present in the char: liquid Ca and solid CaO. Liquid Ca as a condensed phase was dismissed since the char combustion temperature was always greater than the Ca boiling temperature of 1757 K. There are two conceivable calcium vapor species: Ca and CaO.

If the solid CaO within the char is in equilibrium with both the carbon and the gas within the char, then the mole fraction calcium at the inclusion surface is given by the following vaporization reaction:

where:

$$X_{\text{Ca}}^i = K_{5.8} / X_{\text{CO}}^i \quad (5.85)$$

assuming:

- CaO and C have unit activity.

The mole fraction CaO in the gas at the inclusion surface is given by the following vaporization reaction:

where:

$$X_{\text{CaO}}^i = K_{5.9} \quad (5.86)$$

assuming:

- CaO has unit activity.

The total calcium vapor pressure at the inclusion surface is simply the sum of the contributions from each of the above vaporization reactions.

$$P_{\text{Ca},T}^i = P_T X_{\text{Ca},T}^i = X_{\text{Ca}}^i, \text{ rxn 5.8} + X_{\text{CaO}}^i, \text{ rxn 5.9} \quad (5.87)$$

where:

$$X_{\text{Ca},T}^i = \text{total mole fraction of calcium containing vapor species at the inclusion surface}$$

P_T = total pressure = 1 atm

$P_{Ca,T}^i$ = partial pressure of calcium containing vapor species at the inclusion surface.

However, a simple calculation will demonstrate that between 2000 and 3000 K the contribution from Reaction 5.9 is negligible. Thus, for complete, unconstrained equilibrium between the CaO, the carbon, and the gas within the char, Reaction 5.9 can be ignored. Equation (5.85) is plotted in Figure 5.3.8 and represents the partial pressure of calcium at the inclusion surface if equilibrium is achieved with the carbon and the gas within the char.

If the equilibrium is constrained such that neither the solid CaO nor the gas is in equilibrium with the carbon (i.e., the Boudouard reaction is negligible), then the mole fraction calcium at the inclusion surface is given by the following vaporization reaction:

where

$$X_{Ca}^i = \sqrt{K_{5.10} X_{CO}^i} \quad (5.88)$$

assuming:

- CaO has unit activity
- $X_{CO_2} = X_{Ca}$.

Again, a simple calculation will demonstrate that between 2000 and 3000K the contribution from Reaction 5.9 is negligible. Thus, for equilibrium constrained such that neither the gas nor the CaO is in equilibrium with the carbon, Reaction 5.9 can be ignored. Equation (5.88) is plotted in Figure 5.3-8 and represents the partial pressure of calcium at the inclusion surface if equilibrium is achieved between the CaO and the gas within the char only.

Finally, if the equilibrium is constrained such that the CaO does not achieve equilibrium with either the surrounding gas or the carbon, then the only mechanism of vaporization is Reaction 5.9. Equation (5.86) is plotted in Figure 5.3-8 and represents the partial pressure of calcium at the inclusion surface if equilibrium is achieved between the CaO and its vapor only.

A comparison may now be made between the average calcium vapor pressure at the char surface calculated from the data, and the different possible calcium vapor pressures at the inclusion surface. If the calcium is atomically dispersed, the char surface concentration is expected to be equal to the inclusion surface concentration for the case with no reaction in the boundary layer and the char surface concentration is expected to be an order of magnitude smaller than the concentration at the inclusion surface with the maximum reaction

in the boundary layer. From Figure 5.3.8 it is apparent that the only reasonable vaporization mechanism is via Reaction 5.10 which represents equilibrium constrained such that neither the CaO nor the gas are in equilibrium with the carbon. Quann and Sarofim (1982) also concluded that Reaction 5.10 was the dominant vaporization mechanism during pulverized coal combustion. This is supported by the work of Hastings (1984) who reports rates for the Boudouard reaction which are very slow for the temperature and time scale of pulverized coal combustion.

Assuming Reaction 5.10 is the vaporization mechanism, we used Eq. (5.88) in the vaporization model of Subsection 5.3.2.3. Figure 5.3-9 shows the average partial pressure of calcium at the char surface calculated from the model and from the experimental data, both with and without calcium oxidation in the char boundary layer.

FIGURE 5.3-9 - Comparison of the average calcium vapor pressure at the char surface calculated from the data to those calculated from the model

Unfortunately, one input to the calcium vaporization model was unknown. As mentioned at the beginning of this section, the exact form and distribution of the CaO in the char could not be determined. Thus, for the purposes of modeling calcium vaporization, the inclusion size can be thought of as an adjustable parameter representing both the inclusion size and the uniformity of distribution. The model shown in Figure 5.3-9 assumes 0.2 μm diameter CaO inclusions uniformly distributed throughout all char particles. Given the extended duration of the pyrolysis during the char manufacture, inclusions of order 0.1 μm are reasonable.

At the highest temperatures the model is limited by depletion of calcium in the char. This corresponds well with the data. At the lowest temperatures the model overpredicts vaporization. This can be explained by postulating that at the lower temperatures the vaporization reaction (Reaction 5.10) becomes kinetically limited, and, therefore a calcium partial pressure lower than equilibrium is achieved at the inclusion surface. Unfortunately, no kinetics were found for Reaction 5.10 and this hypothesis could not be tested further.

The only other calcium vaporization data available that was suitable for comparison was the Montana lignite data of Quann and Sarofim (1982). Figure 5.3.10 shows the partial pressure of calcium at the char surface calculated from the present data and that calculated from the data of Quann and Sarofim (1982) (both sets of data assume no reaction in the boundary layer). Quann and Sarofim used the temperatures measured by Timothy et al. (1982) to plot their results. As discussed in Subsection 5.3.1.3, the Timothy et al. temperatures were a time-weighted average temperature over burn-out. Large Montana lignite particles ($> 100 \mu\text{m}$) burn as shrinking spheres. As they burn they experience mass-transfer limited combustion during the majority of burnout after which combustion becomes kinetically limited. The mass-transfer limited combustion occurs very rapidly and at a very high temperature which is very close to the maximum temperature. The kinetically limited combustion occurs at a relatively slow rate and at a low temperature and, consequently, reduces the time-weighted average temperature well below the temperature at which most the vaporization occurs. Thus, assuming vaporization is an exponential function of temperature, the data is better interpreted using the maximum temperature rather than the time-weighted temperature. The Quann and Sarofim data was reinterpreted with the maximum temperature and the corrected vaporization results are also plotted on Figure 5.3-10. As can be seen from this figure, once corrected, the Quann and Sarofim results agree well with the present results.

Once again it is important to note that the fact that the results fall below Eq. (5.88) in Figure 5.3-10 indicates that either the calcium is present as finite inclusions or it is nonuniformly distributed or both. In fact, given the tremendous heterogeneity of coal, it would be difficult to believe that the calcium was perfectly uniformly distributed on the atomic scale in all particles all through burn-out.

FIGURE 5.3.10 - Comparison of current calcium vaporization results to the previous results of Quann and Sarofim (1982).

5.3.2.4.3 Silicon

The results which are considered here are those shown in Table 5.3.11 which were produced from a sucrose/carbon black char doped with approximately 4 wt% silica inclusions. The inclusions were between 1 and 5 μm with a mass mean of approximately 4 μm . It should also be noted that the inclusions were, to the best of our ability to measure dispersion, uniformly distributed.

The data presented in the first column of Table 5.3-12 were transformed to the average mole fraction (which is equal to the partial pressure, given the total pressure in all experiments was 1 atm) silicon at the char surface using Eqs. (5.62), (5.74), and (5.77) and are shown in Figure 5.3-11. The average silicon vapor pressures at the char surface shown in Figure 5.3-11 were calculated with Eq. (5.62) which assumes no oxidation of silicon vapor in the char boundary layer. Unfortunately no appropriate gas-phase kinetics could be found for silicon monoxide oxidation. Given the oxidation of silicon monoxide is endothermic under the conditions of interest and that the rate-limiting elementary step is unknown, the rate could not be estimated from kinetic theory. Consequently, only an upper limit of the silicon vapor pressures at the char surface was calculated.

FIGURE 5.3-11 - Calculated average silicon vapor pressure at the char surface during burnout compared to several equilibrium silicon vapor pressure curves assuming silicon dioxide is the condensed phase

The silicon present in the char initially exists as solid silicon dioxide. As the particle heats up the silicon dioxide melts (m.p. approximately 1700 K). At the temperatures of interest (2000 to 3000 K) and in the presence of an excess of carbon with a limited gas phase, the silicon dioxide would be converted to silicon carbide. However, this reaction may be too slow and may not occur on the time scale of pulverized coal combustion. Thus, two condensed phases are considered possible for the silicon vaporization modeling: liquid SiO_2 and solid SiC .

5.3.2.4.3.1 SiO_2 as the condensed phase.

Beginning as with the discussion of calcium vaporization, the first case to consider with SiO_2 as the condensed phase is equilibrium with both the carbon and the gas within the char. However, one notes from the discussion above that if such an equilibrium existed the silicon would be SiC , not SiO_2 . Thus, when SiO_2 is assumed to be the condensed phase, equilibrium has already been constrained such that the carbon is not in equilibrium with SiO_2 . With SiO_2 as the condensed phase there are three possible gas species: Si, SiO , and SiO_2 .

If we assume that the gas within the char is in equilibrium with the carbon and with the SiO_2 , but the SiO_2 and carbon are not in equilibrium, then the mole fraction silicon monoxide at the inclusion surface is given by the sum of the following two reactions:

where:

$$X_{\text{SiO}}^1 = K_{5.8} / X_{\text{CO}}^1 \quad (5.89)$$

assuming:

- SiO_2 and C have unit activity.

The mole fraction Si in the gas at the inclusion surface is given by the sum of the following two reactions:

where:

$$X_{\text{SiO}}^{\text{i}} = K_{5.16} / (X_{\text{CO}}^{\text{i}})^2 \quad (5.90)$$

assuming:

- SiO_2 and C have unit activity.

The mole fraction SiO_2 in the gas at the inclusion surface is given by the following vaporization reaction:

where:

$$X_{\text{SiO}_2}^{\text{i}} = K_{5.17} \quad (5.91)$$

assuming:

- $\text{SiO}_2(\ell)$ has unit activity.

The total silicon vapor pressure at the inclusion surface is the sum of the contributions from each of the above vaporization reactions:

$$P_{\text{Si},\text{T}}^{\text{i}} = P_{\text{T}} X_{\text{Si},\text{T}}^{\text{i}} = X_{\text{Si},\text{T}}^{\text{i}}, \text{ rxn 5.16} + X_{\text{SiO},\text{T}}^{\text{i}}, \text{ rxn 5.13} + X_{\text{SiO},\text{T}}^{\text{i}}, \text{ rxn 5.17} \quad (5.92)$$

where:

$$X_{\text{Si},\text{T}}^{\text{i}} = \text{total mole fraction of silicon containing vapor species at the inclusion surface}$$

$$P_{\text{T}} = \text{total pressure} = 1 \text{ atm}$$

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

6 of 6

$P_{Si,T}^i$ = partial pressure of silicon containing vapor species at the inclusion surface.

However, a simple calculation will demonstrate that between 2000 and 3000 K the contribution from Reaction 5.17 is negligible. Reaction 5.16 dominates at temperatures greater than 2800 K. Reaction 5.4 dominates at temperatures less than 2800 K. Thus, if both the carbon and the SiO_2 are assumed to be in equilibrium with the gas, but the SiO_2 and carbon are not in equilibrium, then Reactions 5.14 and 5.16 are both important. Equation (5.89) and (5.90) are plotted in Figure 5.3-11. If the equilibrium is constrained such that neither the solid SiO_2 nor the gas is in equilibrium with the carbon (i.e., the Boudouard reaction is negligible), then the mole fraction silicon monoxide at the inclusion surface is given by the following vaporization reaction:

where:

$$X_{SiO}^i = \sqrt{K_{5.12} X_{CO}^i} \quad (5.93)$$

assuming:

- SiO_2 has unit activity
- $X_{CO_2} = X_{SiO}$.

The mole fraction Si in the gas at the inclusion surface is given by the following vaporization reaction:

where:

$$X_{Si}^i = \left(K_{5.15} (X_{CO}^i)^2 \right)^{1/3} \quad (5.94)$$

assuming:

- SiO_2 has unit activity
- $1/2 X_{CO_2} = X_{SiO}$.

The total silicon vapor pressure at the inclusion surface is the sum of the contributions from reactions 5.12, 5.15, and 5.18. A simple calculation in this case demonstrates that the contributions from Reactions 5.15 and 5.18 is negligible. Thus, for equilibrium constrained

such that neither the gas nor the SiO_2 is in equilibrium with the carbon, Reactions 5.15 and 5.18 can be ignored. Equation (5.93) is plotted in Figure 5.3-11 and represents the partial pressure of silicon at the inclusion surface if equilibrium is achieved between the SiO_2 and the surrounding gas only.

Finally, if the equilibrium is constrained such that the SiO_2 does not achieve equilibrium with either the surrounding gas or the carbon, then the only mechanism of vaporization is Reaction 5.18. Equation (5.91) is plotted in Figure 5.3-11 and represents the partial pressure of silicon at the inclusion surface if equilibrium is achieved between the SiO_2 and its vapor only.

Figure 5.3-11 may now be used to compare the average silicon vapor pressure at the char surface calculated from the data, and the different possible silicon vapor pressures at the inclusion surface. Given the inclusions were $4\text{ }\mu\text{m}$ in diameter and no reaction was assumed to occur in the char boundary layer, the concentration of silicon containing vapor at the char surface is expected to be 1/10th to 1/100th of the inclusion surface concentration. From Figure 5.3-11 it is apparent that the only reasonable vaporization mechanism is via Reaction 5.12 which represents equilibrium constrained such that neither the SiO_2 nor the gas are in equilibrium with the carbon. Assuming Reaction 5.12 is the vaporization mechanism, we can use Equation (5.93) in the vaporization model of Subsection 5.3.2.3. Figure 5.3-12 shows the average partial pressure of silicon monoxide at the char surface calculated from the model and from the experimental data. Clearly, the model does not fit the data well. Even if a large amount of error is assumed in the inclusion size measurement, this model does not fit the data well.

5.3.2.4.3.2 SiC as the condensed phase.

If SiC is the condensed phase, it must be in equilibrium with the carbon. There are three possible gas species: Si and SiO, and SiC. The mole fraction silicon monoxide at the inclusion surface is given by the following reaction:

where:

$$X_{\text{SiO}}^i = K_{5.19} X_{\text{CO}}^i \quad (5.95)$$

assuming:

- SiC and carbon have unit activity.

FIGURE 5.3.12 - Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from the silicon dioxide model.

The mole fraction silicon at the inclusion surface is given by the following reaction:

where:

$$x_{\text{Si}}^i = K_{5.20} \quad (5.96)$$

assuming:

- SiC and carbon have unit activity.

The mole fraction silicon carbide vapor at the inclusion surface is given by the following reaction:

where:

$$x_{\text{SiC}}^i = K_{5.21} \quad (5.97)$$

assuming:

- SiC has unit activity.

The total silicon vapor pressure at the inclusion surface is the sum of the contributions from each of the above three vaporization reactions. However, a simple calculation demonstrates that between 2000 and 3000 K the contribution from Reaction 5.21 is negligible. Reaction 5.20 dominates at temperatures greater than 2800 K. Reaction 5.19 dominates at temperatures less than 2800 K. Thus, both Reactions 5.19 and 5.20 are possible vaporization reactions. Equations (5.95) and (5.96) are plotted in Figure 5.3-13 along with the average silicon vapor pressure at the char surface calculated from the experimental data.

Figure 5.3-13 may now be used to compare the average silicon vapor pressure at the char surface calculated from the data, and the different possible silicon vapor pressures at the inclusion surface. Given the inclusions were 4 μm in diameter and no reaction was assumed to occur in the char boundary layer, the concentration of silicon containing vapor at the char surface is expected to be 1/10th to 1/100th of the inclusion surface concentration. From Figure 5.3-13 it is apparent that when the condensed phase is assumed to be SiC, the only reasonable vaporization mechanism is via Reaction 5.19. Assuming Reaction 5.19 is the vaporization mechanism, Eq. (5.95) was used in the vaporization model of Subsection 5.3.2.3. Figure 5.3-14 shows the average partial pressure of silicon monoxide at the char surface calculated from the model and from the experimental data. At the higher temperatures the model fits the data very well. At the lower temperatures the model overpredicts vaporization. This can be explained by postulating that at the lower temperatures the vaporization reaction (Reaction 5.19) becomes kinetically limited, and, therefore a silicon monoxide partial pressure lower than equilibrium is achieved at the inclusion surface. Unfortunately, no kinetics were found for Reaction 5.19.

FIGURE 5.3-13 - Calculated average silicon vapor pressure at the char surface during burnout compared to several equilibrium silicon vapor pressure curves assuming silicon carbide is the condensed phase.

5.3.2.4.3.3 Kinetic Control

The best model assuming a vaporization reaction in equilibrium at the surface of an SiO_2 inclusion (Reaction 5.12) overpredicted the experimental results at all temperatures (see Figure 5.3-12). The best model assuming a vaporization reaction in equilibrium at the surface of an SiC inclusion (Reaction 5.19) fit the experimental results well at the higher temperatures, but overpredicted the experimental results at the lower temperatures (see

FIGURE 5.3.14 - Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from the silicon carbide model.

Figure 5.3-14). The most reasonable hypothesis is that at low temperatures the kinetics of Reaction 5.12 or 5.19 limit vaporization. At the higher temperatures all the SiO_2 is converted to SiC , Reaction 5.19 is in equilibrium at the inclusion surface, and diffusion limits vaporization. This hypothesis is supported by the work of Padia, 1976 and Turkdogan et al., 1980. Padia and Turkdogan performed experiments heating samples containing silica and carbon to temperatures of greater than 1900 K for times of 10 to 120 min. Padia found that the conversion of SiO_2 to SiC was very temperature sensitive and that silicon vaporization dropped dramatically once SiC was formed. Turkdogan concluded that in the

absence of sulfur, silica was converted to SiC, and that silicon vaporization from SiC was controlled by the equilibrium of Reaction 5.12.

In order to test this hypothesis, models of vaporization assuming kinetic control of either Reaction 5.12 or 5.19 were desired. Unfortunately, kinetic data was found for Reaction 5.12 only. Ozturk and Fruehan, 1985, measured the rate of Reaction 5.12 at 1923 K and Schwerdtfeger, 1966, measured the rate of Reaction 5.12 at 1773 K. Unfortunately, the rate data for Reaction 5.12 exists only over a very narrow temperature range and was produced by different experimentalists, with different equipment, under different conditions. Consequently, an accurate estimate of the activation energy of Reaction 5.12 could not be made. In order to complete a model based on vaporization via kinetically limited Reaction 5, activation energies of 120 and 160 kcal/mole, which represented 100 and 130% of the change in standard enthalpy for Reaction 5, were used.

Figure 5.3-15 shows the average partial pressure of SiO at the char surface calculated from the data as well as that calculated from three different models. The different models were based on (1) diffusion control with Reaction 5.12 in equilibrium at the inclusion surface, (2) diffusion control with Reaction 5.19 in equilibrium at the inclusion surface, and (3) kinetic control based on Reaction 5.12 at the inclusion surface. The previous hypothesis of kinetic, or combined kinetic and diffusive control of Reaction 5.12 or 5.19 at low temperatures, and diffusion control with Reaction 5.19 in equilibrium at high temperatures, is supported by Figure 5.3-15. Assuming that the above hypothesis does qualitatively describe silicon vaporization from the synthetic chars of this thesis, one immediately notes the difficulty of developing a predictive silicon vaporization model. A predictive model for the idealized char of SiO₂ and carbon only would require the additional knowledge of Reaction 5.12 kinetics, Reaction 5.19 kinetics, and the kinetics of SiC formation. A predictive model for coal would be even more difficult noting that (1) estimating the rate of SiC formation would be severely complicated by the variety of forms and compositions of SiO₂ that may exist in coal and (2) the influence of sulfur, which was seen in Table 5.3-11 to be significant, may be difficult to predict quantitatively.

5.3.2.4.3.4 Comparison to Previous Work

Three sets of silicon vaporization results were found which were suitable for comparison. The results of Quann and Sarofim (1982) for 130 μm Montana lignite and Illinois #6 bituminous coal, and the results of Senior and Flagan for 38 to 61 μm microporous synthetic chars with 9 wt% 1 to 5 μm SiO₂ inclusions are plotted in Figure 5.3-16 along with the present results. As with the calcium results from the Quann and Sarofim Montana lignite data, the combustion temperatures were corrected from the time-averaged temperatures to the maximum temperatures. However, because the Illinois #6 burns as a cenosphere ($\therefore$ the time-averaged temperatures $\cong$ maximum temperatures) no temperature correction was necessary (see Subsection 5.3.1.3 for further discussion).

FIGURE 5.3.15 - Comparison of the average silicon vapor pressures at the char surface calculated from the data to those calculated from three different models.

Silicon vaporization from Illinois #6 appears to be a factor of 5 to 10 greater than that from Montana lignite after correction. This can be explained by a number of reasons: Illinois #6 has smaller SiO_2 inclusions, a shorter diffusion length (burns as a cenosphere), 5 times as much pyritic sulfur, and 2 times as much organic sulfur. Smaller inclusions and a shorter diffusion length increase vaporization in general. High sulfur levels increase the likelihood of the additional vaporization mechanism via SiS .

FIGURE 5.3.16 - Comparison of current silicon vaporization results to previous results.

The difference between the present results and the coal results can be rationalized a number of ways: (1) The coals contain sulfur and the dominant vaporization mechanism in the presence of a high sulfur pressure may be via SiS (Turkdogan, 1980). (2) The SiO₂ in the coals may be converted to SiC more slowly than the SiO₂ in the synthetic chars because the coals contain larger SiO₂ particles with many impurities and many aluminosilicates. Vaporization via the carbide is much slower than via the oxide (see Figure 5.3-15). (3) Finally, the coals have a much broader pore size distribution which reduces the diffusional barrier to vaporization.

The synthetic char results of Senior and Flagan (1984) and the results of this thesis should be quite similar. The only significant difference in the experiments is that Senior and Flagan used smaller char particles with smaller pores. Indeed, the results are quite similar at the lower temperatures. However, at the higher temperatures, Senior and Flagan show much higher vaporization rates. This may be explained by the fact that Senior and Flagan modeled char combustion and plotted their results with "mean particle temperatures". How the mean was calculated is not reported and not enough information is given in their paper to recalculate the char temperatures. Thus, if the mean temperatures were significantly lower than the maximum temperatures, their results should be corrected as were the Quann and Sarofim results for Montana lignite. With such a correction the Senior and Flagan results may match the present results much more closely.

Re-examining the conclusions of previous researchers, one finds that Quann and Sarofim concluded that Reaction 5.12:

is in equilibrium at the inclusion surface and vaporization is strictly diffusion limited. Senior and Flagan concluded that Reaction 5.12 was not equilibrated and; therefore, SiO_2 vaporizes directly (Reaction 5.18) rather than undergoing reduction to SiO .

As discussed by Quann and Sarofim, Reaction 5.12 may be the vaporization reaction, especially at low temperatures. However, equilibrium of Reaction 5.12 is doubtful at the lower temperatures, SiC is likely to be important at high temperatures, and vaporization as SiS must be considered when dealing with coals.

As discussed by Senior and Flagan, Reaction 5.12 is not equilibrated, especially at the lower temperatures. However, just because Reaction 5.12 is not equilibrated does not imply that it is not the vaporization mechanism. Furthermore, the diffusional resistance within the char cannot be ignored. In other words, direct vaporization of SiO_2 would require that the SiO_2 vapor pressure be 1 to 2 orders of magnitude greater than the average partial pressure of silicon at the char surface calculated from the data. Clearly this is not the case for any of the results shown in Figure 5.3-16

5.3.2.4.4 Iron

The results which are considered here are those shown in Table 5.3-13 which were produced from a sucrose/carbon black char doped with approximately 4 wt% pyrite inclusions. The inclusions were between 1 and 5 μm with a mass mean of approximately 4 μm . It should also be noted that the inclusions were, to the best of our ability to measure dispersion, uniformly distributed.

The data presented in the first and second column of Table 5.3-13 were transformed to mole fraction (which is equal to the partial pressure, given the total pressure in all experiments was 1 atm) iron at the char surface using Eqs. (5.62), (5.69), (5.74), and (5.77)

and are shown in Figure 5.3-17. The data are reported twice in Figure 5.3-7. The upper set of data assumes no oxidation of iron vapor in the char boundary layer (case 1, Eq. (5.62), and the lower set assumes the maximum oxidation rate of iron in the boundary layer (case 2, Eq. (5.69). The gas-phase oxidation kinetics were taken from the literature (Fontijn et al., 1973). The maximum rate was estimated using the particle temperature and the bulk O_2 concentration.

The data in Table 5.3-13 show that as much as 50 to 60 wt% of the iron appears in the submicron ash at 30% O_2 and that this percentage increases by only 10% as the O_2 concentration is increased from 30 to 80%. This is a strong indication that vaporization may be limited by depletion of the iron in the char during burn-out. For this reason, the maximum average partial pressure of iron at the char surface was calculated by assuming all

FIGURE 5.3-17 - Calculated average iron vapor pressure at the char surface during burnout compared to equilibrium iron vapor pressure curves assuming iron oxide is the condensed phase.

the iron vaporizes. This maximum is plotted in Figure 5.3-17. Indeed, it appears from Figure 5.3-17 that iron depletion may limit iron vaporization at particle temperatures greater than 2500 K (30% O₂).

In order to understand what condensed phases of iron may be present during combustion, one must consider what transformations the pyrite undergoes as the char particle burns out. Pyrite (FeS₂) will lose one sulfur between 770 and 970 K to become pyrrhotite (FeS) (Levassuer et al., submitted). Pyrrhotite melts at 1450 K. As shown in Figure 5 3-18 the sulfur in pyrrhotite has a significant vapor pressure at temperatures above 1450 K (Burgmann et al., 1968). The vapor pressure of sulfur will be increased further as carbon dissolves into the Fe-S melt. When saturated with carbon, the activity of sulfur in liquid iron is increased by approximately a factor of 10. Thus, sulfur is expected to vaporize rapidly from the liquid pyrrhotite melt resulting in a non-stoichiometric melt and possibly liquid iron. The rate of sulfur loss is further complicated by the fact that the char matrix itself may trap sulfur lost from the pyrite or pyrrhotite, Cleyle et al. (1984). Eventually the non-stoichiometric Fe-S melt or liquid iron (depending on the rate of sulfur loss) will be exposed to the oxidizing atmosphere outside the char particle and will be converted to FeO. Thus, we will consider iron vaporization from three different condensed phases: FeO, Fe, and FeS.

5.3.2.4.4.1 Iron Oxide as the Condensed Phase.

FeO is similar in many respects to CaO. If both the gas in the char and the char are assumed to be in equilibrium with the FeO, then Fe vapor is the dominant gas species and the equilibrium can be described by the following reaction:

where:

$$X_{\text{Fe}}^i = K_{5.22} / X_{\text{CO}}^i \quad (5.98)$$

assuming:

- FeO and C have unit activity.

However, as with CaO, equilibrium of the reduction by carbon produces an unrealistically high vapor pressure at the inclusion surface. Thus, as was the case with CaO, this was ignored as a possible driving force and two different constraints on equilibrium are considered.

FIGURE 5.3-18 - Fe-S phase diagram (Burgmann et al., 1978).

If equilibrium is constrained such that neither the gas in the char nor the FeO is in equilibrium with the carbon (i.e., the Boudouard reaction is negligible), then Fe vapor is still the dominant gas species, but the equilibrium is given by the following reaction.

where:

$$X_{\text{Fe}}^{\text{I}} = \sqrt{K_{5.23}/X_{\text{CO}}^{\text{I}}} \quad (5.99)$$

assuming:

- FeO has unit activity
- $X_{\text{Fe}} = X_{\text{CO}_2}$

Finally, if equilibrium is constrained such that FeO does not achieve equilibrium with either the surrounding gas or the carbon, then the only mechanism of vaporization is Reaction 5.24:

where:

$$X_{\text{Fe}}^{\text{I}} = K_{5.18} \quad (5.100)$$

assuming:

- FeO has unit activity.

Equations (5.99) and (5.100) have been plotted in Figure 5.3-17 for comparison with the average partial pressure of iron at the char surface calculated from the data. Given the inclusions had a mass mean diameter of 4 μm , Equation (5.71) indicates that if no iron oxidation occurs in the char boundary layer, then the concentration of iron vapor at the char surface should be 1/10 to 1/100 of the inclusion surface concentration. Equation (5.73) indicates that if the maximum iron oxidation rate is assumed throughout the char boundary layer, then the concentration of iron vapor at the char surface should be 1/100 to 1/1000 of the inclusion surface concentration.

Given the above requirements, Figure 5.3-17 demonstrates that Reaction 5.24 cannot be the vaporization mechanism. Based strictly on Figure 5.3-17, Reaction 5.23 appears viable. However, Reaction 5.23 deserves more thought. How did the oxide form? The oxide is expected to form only on the char surface or after char burn-out is complete. Therefore Reaction 5.23 cannot be the vaporization mechanism and FeO is disregarded as a possible condensed phase from which iron vaporizes.

5.3.2.4.4.2 Fe as the Condensed Phase.

With liquid iron as the condensed phase there is only one possible vaporization reaction:

where:

$$\begin{aligned} X_{\text{Fe}}^i &= K_{5.25} a_{\text{Fe}} \\ a_{\text{Fe}} &\approx 0.6 \end{aligned} \quad (5.101)$$

Equation (5.101) is plotted in Figure 5.3-19 along with the average partial pressure of iron at the char surface calculated from the data for comparison. Iron vaporization from liquid iron appears to be a reasonable vaporization mechanism and Equation (5.101) was used with the model of Subsection 5.3.2.3 to predict the average partial pressure of iron at the char surface. A comparison of the average surface pressure calculated from the model and the data is given in Figure 5.3-20. The model underpredicts vaporization at all temperatures below 2800 K.

5.3.2.4.4.3 FeS as the Condensed Phase

With FeS as the condensed phase there are only two possible vaporization reactions:

where:

$$X_{\text{FeS}}^i = K_{5.26} \quad (5.102)$$

assuming:

- FeS has unit activity.

FIGURE 5.3.19 - Calculated average iron vapor pressure at the char surface during burnout compared to the equilibrium iron vapor pressure curve assuming iron is the condensed phase.

rxn 5.27

where:

$$x_{\text{Fe}}^i = K_{5.27} / \sqrt{P_{\text{S}_2}}$$

(5.103)

FIGURE 5.3-20 - Comparison of average iron vapor pressures at the char surface calculated from the data to those calculated from the iron model.

assuming:

- FeS has unit activity.

Both Eqs. (5.102) and (5.103) are plotted in Figure 5.3-21 for comparison to the average partial pressure of iron at the char surface calculated from the data. From Figure 5.3.21 it is clear that reaction 5.26 is not a viable vaporization mechanism. However, depending on the S_2 pressure, Reaction 5.27 can fit the data. Thus, the question becomes "what sulfur pressures are reasonable?"

FIGURE 5.3-21 - Calculated average iron vapor pressure at the char surface during burnout compared to several equilibrium iron vapor pressure curves assuming iron sulfide is the condensed phase.

An estimate of the sulfur pressure at the inclusion surface was calculated based on the following assumptions:

1. The only sulfur gas species is S_2 .
2. The S_2 pressure at the inclusion surface is constant throughout char burnout.

3. The sulfur from the pyrite to pyrrhotite transformation is accomplished during pyrolysis and is not present during char combustion.
4. The moles of sulfur (S_2) which vaporize from the pyrrhotite melt during combustion is equal to 1/2 the moles of iron vaporized.
5. The sulfur vaporization is controlled by diffusion of the sulfur from the inclusion surface through the char and through the char boundary layer into the bulk gas.
6. Char combustion is suitably described by the char combustion model of Subsection 5.3.1.2.
7. Sulfur vaporization can be suitably described by the model of Subsection 5.3.2.3 used to describe metal vaporization.
8. No sulfur is oxidized in the char boundary layer.

With this approximation of the S_2 pressure at the inclusion surface, the results of the iron vaporization model are shown in Figure 5.3-22. Figure 5.3-22 shows that with these assumptions, Reaction 5.27 could be responsible for the iron which appears in the submicron ash.

In reality, the sulfur vapor pressure at the inclusion surface may vary from 1 atm during the initial stages of burnout to near zero the end of burnout, the carbon matrix within the char may temporarily absorb sulfur (Cleyle et al., 1984), the ratio of the moles of S_2 /mole Fe vaporized during char combustion is probably not exactly 1/2, and sulfur is probably oxidized to some extent in the char boundary layer. Thus, the iron vaporization modeling is crude and is not meant to indicate that this is the correct mechanism, but rather that it could be the mechanism by which iron appears in the submicron ash.

Obviously, the situation is complex with the sulfur pressure changing continuously through burn-out. What little modeling can be done for such a complex system suggests that iron vaporization as atomic Fe from a rapidly changing Fe-S-C melt can account for the iron vaporization observed experimentally. On the other hand, the modeling does not preclude other mechanisms which could be responsible for the "apparent vaporization" such as the loss of small iron fragments or droplets during the pyrite to pyrrhotite transformation.

5.3.2.4.4 Comparison to Previous Work

Two sets of iron vaporization results were found which were suitable for comparison. The results of Quann (1982) for 130 μ m Montana lignite and Illinois #6 bituminous coal are plotted in Figure 5.3-23 along with the present results. As with the calcium results from the Quann and Sarofim Montana lignite data, the combustion temperatures were corrected from the time-averaged temperatures to the maximum temperatures. However, because the Illinois

FIGURE 5.3.22 - Comparison of average iron vapor pressure at the char surface calculated from the data to those calculated from the iron sulfide model.

#6 burns as a cenosphere ($\therefore$ the time-averaged temperatures $\cong$ maximum temperatures) no temperature correction was necessary.

The corrected iron vaporization results from Montana lignite shown in Figure 5.3-23 are consistently lower than the synthetic char results by approximately 1 order of magnitude. This can be explained by the fact that the synthetic char contained four times more pyrite than Quann's Montana lignite and the pyrite in the synthetic char was present as smaller inclusions.

FIGURE 5.3-23 - Comparison of current iron vaporization results to the previous results of Quann (1982).

The Illinois #6 results peak at the same level as the synthetic char which is consistent with the fact that both chars contained approximately the same amount of pyrite. The vaporization results from the Illinois #6 at the lower temperatures can be explained by the fact that the Illinois #6 contained twice as much sulfur as did the synthetic char (Illinois #6 contained both inorganic and organic sulfur while the synthetic char contained only inorganic sulfur). The higher sulfur vapor pressure shifted the equilibrium of Reaction 5.26 to the left, thereby reducing the iron vapor pressure at the inclusion surface.

5.3.2.5 Summary of Vaporization Study

No evidence indicating that the mechanism of submicron ash formation was anything other than vaporization was found.

Calcium

- Significant calcium vaporization occurs via finely dispersed calcium only.
- The presence of sulfur slightly inhibits vaporization, presumably due to the formation of the sulfide.
- Calcium vaporization occurs via reduction of CaO by CO.
- The CO reduction reaction is in equilibrium above 2500 K, below 2500K reduction kinetics becomes important.
- The calcium partial pressure at the char surface is always below that predicted by equilibrium of the CO reduction reaction due to calcium being present as small inclusions or being nonuniformly distributed or both.

Silicon

- Vaporization of silicon is slightly reduced if present as aluminosilicates or if in the presence of sodium.
- The presence of sulfur increases silica vaporization, especially at low oxygen concentrations.
- At temperatures below 2500 K and in the absence of sulfur, silicon vaporizes as silicon monoxide and is due to the kinetically limited reaction of CO with silica or silicon carbide.
- At temperatures above 2500 K and in the absence of sulfur, silicon vaporization is as silicon monoxide and is due to the equilibrium of reaction of CO with SiC.

Iron

- Iron vaporization occurs primarily from intrinsic pyrite, not extraneous pyrite.
- Intrinsic pyrite becomes an $\text{Fe}_{1-x}\text{-S}$ melt during char combustion. Iron vaporization from intrinsic pyrite occurs via the vapor pressure of atomic iron over the $\text{Fe}_{1-x}\text{-S}$ melts.
- Iron vaporization is unaffected by the presence of finely distributed calcium.

5.4 Residual Ash Formation

5.4.1 Beneficiated Coal Performance in a Laminar Flow Reactor

5.4.1.1 Sample Preparation

The sample preparation procedure was first to dry the as-received coal samples to avoid agglomeration of coal particles during feeding into the furnace, and then to air-classify by Acucut to remove fine coal particles (less than $10\text{ }\mu\text{m}$ in diameter). Size classification of the samples was then carried out to 63 to $75\text{ }\mu\text{m}$ using a Ro-tap sieve machine. Of the samples provided for the test, the samples prepared thus were Gravimelt 7A, Gravimelt 9C, Loy Yang 1953, and a blend of 70% Eagle Butte/30% Kentucky No. 9. All of these samples are discussed in more detail in Sections 3 and 4 of this report. The Illinois No. 6-based SOAP coal could not be tested since it could not be dried. Due to the practical limitations of the feeder system, samples have to be dried before feeding. When the drying of the Illinois No. 6-based SOAP coal was attempted in an oven of 120°C , the coal ignited. It is believed that this was caused by residual cleaning medium (heptane) that was retained by the coal particles in the cleaning process.

5.4.1.2 Ash Mass Distributions

The samples thus prepared were tested in a drop tube furnace at a gas temperature of 1650 K and gas composition of 20, 50, and 80% O_2 in N_2 . The material balance for the mineral matter in coal was closed. The ash mass distributions obtained from cascade impactor runs are shown in Figures 5.4-1 to 5.4-4. Three modes are conspicuous in the ash mass distributions. Each of the distributions can be broken down to three modes. These modes are generated by different formation mechanisms. Submicron mode (less than $1\text{ }\mu\text{m}$) is generated by vaporization and condensation of mineral matter; fragmentation mode (between 1 and $7\text{ }\mu\text{m}$) by fragmentation of char and partial coalescence of mineral matter; and residual ash mode (greater than $7\text{ }\mu\text{m}$) by coalescence of mineral matter during char combustion. The ash mass distributions divided into these three modes are reported in Table 5.4-1.

For the chemically cleaned Gravimelt coals at 20% O_2 , over 60 wt% of the total ash was in the submicron mode, which is a significant fractional increase when compared with uncleaned coals. For example, the submicron ash fraction of Gravimelt 7A at 20% O_2 is 61 wt% whereas that of its parent coal, i.e., uncleaned Kentucky No. 9 coal, is only 7.3 wt%.

The two Australian coals, Loy Yang 1953 and Loy Yang 2301, produced ash mass distributions significantly different from each other. As with the cleaned versus uncleaned Kentucky No. 9 coals, the difference is shown mainly in the submicron range. The fraction of submicron ash for Loy Yang 1953 (Phase II coal) is 32.7 wt% whereas that for Loy Yang 2301 (Phase I coal) is 40.7 wt%.

FIGURE 5.4-1 - Inverted ash mass distributions of Gravimelt 7A (Kentucky #9) as measured by cascade impactor runs at different conditions.
63/75 μm coal sample.

FIGURE 5.4-2. - Inverted ash mass distributions of Gravimelt 9C (Pittsburgh 8) as measured by cascade impactor runs at different conditions.
63/74 μm coal sample.

FIGURE 5.4-3 - Inverted ash mass distributions of Loy Yang 1953 as measured by cascade impactor runs at different conditions. 63/75 μm coal sample.

FIGURE 5.4-4 - Ash mass distributions of 70/30 Blend (EB/Ky 9) by the cascade impactor runs at different conditions. 63/75 μm coal sample.

**TABLE 5.4-1. - Ash mass distributions of tested coals by three different modes
(gas temperature = 1650 K)**

Coal Type	% O ₂	Submicron Ash Mode (< 1 μm) (wt%)	Fragmentation Mode (1 to 7 μm) (wt%)	Residual Ash Mode (> 7 μm) (wt%)
Gravimelt 7A	20	61	10.7	28.9
	50	68	13.9	18.3
	80	72.8	14.4	13.0
Kentucky No. 9	20	7.3	5.4	90.8
Gravimelt 9C	20	64.1	28.7	7.3
	50	89.2	8.3	2.2
	80	81.9	18.0	0.2
Loy Yang 1953	20	32.7	31.5	36.9
	50	61.5	12.4	27.3
	80	83.8	9.7	6.6
Loy Yang 2301	20	40.7	23.0	36.3
Blend (EB/Ky 9)	20	9.7	23.0	69.5
	50	26.7	28.9	46.3
	80	40.5	26.7	34.4
Eagle Butte	20	13.6	31.8	54.6
Blend*	20	12.0	25.2	63.8
*Average of Eagle Butte and Kentucky No. 9 data weighted by the blending ratio.				

At 20% O₂, the blend (EB/Ky9) produced about 10 wt% of the total ash as submicron ash, which is comparable to the average of the submicron ash fractions of Eagle Butte and Kentucky No. 9 weighted by their blending ratio.

The effect of coal cleaning on the preferential increase of the submicron ash fraction is quite favorable for the mitigation of slagging problems in terms of inertial impaction. This submicron portion, however, can cause serious deposition problems by being deposited onto the internal surfaces of boilers through condensation or thermophoresis. The submicron ash particles thus formed can also affect the performance of particulate control equipment such as electrostatic precipitator or baghouses.

5.4.1.3 Chemical Analysis on Submicron Ash

Chemical analysis was performed on submicron ash samples collected at 1650 K, 20% O₂. The elements analyzed were sodium, potassium, calcium, and chlorine. The analysis was carried out by induction-coupled plasma in Galbraith Laboratories, TN.

As shown in Table 5.4.2, a significant amount of sodium was found in the submicron ash for the chemically cleaned coals. Submicron ash from Loy Yang and Blend also had a considerable amount of sodium. This significant enrichment of sodium in submicron ash may pose fouling problems. The amount of the other elements of the samples from the four coals, however, was not nearly as much as that of sodium.

TABLE 5.4.2. - Chemical analysis results on submicron ash

Coal Type	Sodium (wt% Na)	Potassium (Wt% K)	Calcium (wt% Ca)	Chlorine (wt% Cl)
Gravimelt 7A	36.5	6.9	4.8	12.1
Gravilment 9C	86.5	5.9	5.9	*
Loy Yang	26.0	6.2	1.5	3.1
Blend (EB/Ky 9)	17.1	1.8	1.8	*
*Below detection limit. Analysis was done by inductively coupled plasma in Galbraith Laboratories.				

5.4.1.4 Pore Structure and its Change by Coal Cleaning

Coal particles treated with chemicals during cleaning process can undergo chemical transformation to the extent that their combustion behavior is affected. One of the effects of the transformation is the change in the chemical composition of carbon matrix, which will in turn affect the devolatilization behavior. The char particles produced from the cleaned coal may have a pore structure different from that of its parent coal particles due to this change. To investigate the effect of the chemical cleaning on the char structure, and eventually on the formation of final ash particles, microscopic study was performed on char samples of Gravimelt 7A and its parent coal, Kentucky No. 9 bituminous coal. The char samples were obtained by pyrolysis of these two coals of size fraction 63/75 μm at 1650 K in pure nitrogen.

The cross-sectional images in Figure 5.4-5 show significant structural difference between these two char samples. The char from Kentucky No. 9 bituminous coal (uncleaned coal) was very thin-walled with a large void space in its center, while that from Gravimelt

FIGURE 5.4-5 - Cross-sectional Images of Chars from Gravimelt 7A (upper) and Kentucky No. 9 bituminous coal (lower)

7A maintained its original shape with a number of spherical (circular in 2-D) macropores distributed in the char matrix. The approximate bulk porosities of the two char samples were obtained from a simple calculation of taking the ratio of the cross-sectional areas of pores and char matrix. The porosities of chars of cleaned (Gravimelt 7A) and uncleaned (Kentucky No. 9) coals obtained thus were approximately 0.24 and 0.68, respectively.

The structural change in char effected by the coal cleaning process is in favor of the interaction and coalescence of mineral inclusions during char combustion. Previous experimental studies (Kang, 1991) show that given that the mineral distributions are the same, more macroporous and cenospheric char produces smaller and less residual ash than less macroporous and non-cenospheric char, and that the effect of pore structural difference is second to the effect of particle-to-particle variation of mineral content.

In other words, the macropore structure of a char, which influences the ash formation process by inducing char fragmentation and by controlling the extent of ash coalescence, can

affect the final ash mass distribution only when other factors controlling the final distribution are not significantly important. As the particle-to-particle variation of mineral content in coal becomes significant, the final ash mass distribution becomes dominated mainly by that variation. As the overall mineral inclusion distribution in coal becomes wide, the final ash mass distribution becomes dominated by the initial mineral distribution. As the coal size distribution becomes wide, the final ash mass distribution becomes dominated by the initial mineral distribution.

5.4.2 Effect of Char Structure on Final Ash Distributions

The effect of pore structure on residual ash formation was studied by burning a Kentucky No. 9 bituminous coal in a laminar flow reactor. Two batches of char samples were prepared from size- and density-classified coal heat-treated at different conditions. Different pore structures - non-cenospheric and cenospheric with respective macroporosities of the carbonaceous structure of 0.076 and 0.89 - were produced by the heat treatment. Experiments were carried out in a highly controlled condition. Modeling studies were done with the modified percolative fragmentation model developed previously in order to further understand the effect of the porosity and the pore distribution.

Part of the experimental work in this line of study has already been reported in the previous final report. The work has been completed during the Phase II of the project. For the purpose of completeness of this work, the results recently obtained along with the work completed during the Phase I are presented.

5.4.2.1 Background

The studies of mineral matter transformation during coal combustion are motivated by concern with fouling and slagging in utility boilers. Previous studies have shown that many factors control the final ash particle size and composition distributions: mineral content, mineral distribution among pulverized coal particles (Charon et al., 1990; Barta et al., 1989), coal particle size distribution (psd) (Holve, 1986), char structure and burnout mechanism (Monroe, 1989; Wibberley and Wall, 1986), viscosity and surface tension of ash particles. This paper will provide additional evidence, experimental and computational, to support recent experimental and simulation studies (Helble and Sarofim, 1990; Kang, et al. 1988) showing that the fragmentation of char induced by macropores can influence the final ash psd.

5.4.2.2 Experimental

Two chars with different pore structures and essentially the same mineral sizes and compositions were carefully prepared by pyrolyzing size-classified (Phase I) Kentucky No.9 bituminous coal at different heating rates, as shown schematically in Figure 5.4-6. A Kentucky No. 9 bituminous swelling coal, air-classified and dry-sieved to 63 to 75 μm , was density-classified into five density fractions using different halogenated methanes. Of the five density fractions, the fraction between 1.32 and 1.36 g/cm^3 was used for the

FIGURE 5.4-6. - Schematic diagram of experimental procedure for studies on the effect of the char burnout mechanism on residual ash formation.

experiment. This procedure was employed to minimize the particle to particle variation in mineral content of the coal sample. The mineral content of each density fraction was determined in a thermogravimetric analyzer.

The size- and density-classified coal was then divided into two batches. Each batch was heat-treated at different temperatures and heating rates in order to produce different pore structures. One batch of the coal was burned in a furnace at 1650 K in a 50% O₂ in N₂ mixture with the high O₂ levels selected to ensure complete combustion. The other batch of the density-separated coal was heated in a pyrolysis furnace to 800°C at a heating rate of 0.1°C/s, and then oxidized at the same condition as that for the first batch of coal. In order to assess the effect of heating rate on pore structure (see Figure 5.4-7) a small portion of the coal was devolatilized at 1650K in N₂ in the laminar flow reactor (1s residence time). Also, a small portion of the slowly pyrolyzed char was devolatilized in the oxygen-free laminar flow reactor at 1650 K to examine its char structure and ensure no further change of pore structure during combustion. Final ash particles were collected with an eight stage Andersen cascade impactor. Three runs were made for each condition. The averaged cascade impactor data were deconvoluted with a modified Twomey algorithm to obtain a smooth size distribution (Twomey, 1975; Kang, 1991; Boni et al., 1990).

C-1715

FIGURE 5.4-7. - Cross-sectioned images of char particles at various preparation stages.

Characterization of the char structure of the two samples was carried out by digital image processing on polished cross-sections of the char particles imbedded in epoxy assuming that the pores are circular in shape.

A stereological analysis (Zygourakis and Glass, 1988; Wicksell, 1925) was used to obtain the three-dimensional pore size distribution from two-dimensional data. When spheres of radius, r , distributed randomly in a three-dimensional space with a probability density function $N(r)$ are intersected by a plane of random orientation, a collection of circles is generated on the plane with their radius, r , randomly distributed between 0 and r_m , and with a probability density function, $n(r)$. The two probability density functions $N(r)$ and $n(r)$ are related to each other as follows (Wicksell, 1925).

$$n(\rho) d\rho = \int_{\rho}^{r_m} \frac{2 N(r) \rho dr}{\sqrt{r^2 - \rho^2}} \quad (5.104)$$

The integral equation was converted into a set of linear equations by discretizing the problem and employing a trapezoidal integration rule (Zygourakis and Glass, 1988).

5.4.2.3 Sample Characterization

5.4.2.3.1 Density Variation

The coal density varied from 1.2 to 5.5 g/cc (Figure 5.4-8). About 90 wt% of the coal had density less than 1.58 g/cc. The mineral content of the different density fractions varied from 3.6 wt% up to 67.5 wt%. In order to eliminate the influence of this wide variation on our experimental result, the density fraction, 1.32 to 1.36 g/cc with a mineral content of 4.6%, was used. Ninety five percent of the mass (number) of the mineral inclusions in the coal were between 2 and 30 μm (0.7 and 6 μm), with a mass (number) mean diameter of 10 μm (2 μm) as measured by a computer-controlled SEM for slowly-pyrolyzed char. The larger mineral particles, however, have been shown to fragment for this coal (Boni et al., 1990).

FIGURE 5.4-8. - The density distribution and mineral content variation of the air-classified, and size-classified Kentucky No. 9 bituminous coal (63 to 75 μm).

5.4.2.3.2 Char Structure

The char morphology of swelling bituminous coals is influenced by their temperature history. When bituminous coal particles are rapidly heated, large intraparticle voids are formed as coal particles go through the liquid metaplast state (between 300° and 500°C), and volatile gas bubbles nucleate and grow within the molten coal particles. The voids thus generated tend to have spheroidal shapes ranging in size from several angstroms to the size of parent coal particles. On the other hand, when the same swelling coal particles are heated up slowly so that the volatiles are released at a much slower rate, they form chars that are less macroporous.

The raw coal particles have faceted surfaces reflecting the cleavage occurring during pulverization. Char particles generated by rapid pyrolysis at 1650 K in the laminar flow reactor have the rounded smooth surfaces expected of cenospheres, whereas those generated at slow pyrolysis rates have faceted faces similar to those in the raw coal particles. The effect of the heat treatment on the char morphology is clearly shown in the digitized image of the cross-sectioned char particles of Figure 5.4-7. Rapidly-pyrolyzed char particles have many small vesicles with sizes between 1 and 15 μm around a large void in the center, and have thin walls prone to fragmentation. Slowly-pyrolyzed char, on the other hand, is less macroporous, and has smaller pores and average pore-to-pore distances. This type of char is expected to fragment less than the highly macroporous, thin-walled char. The probability of the ash coalescence is also higher for this type of char compared with the rapidly-pyrolyzed char.

The volatile yield is 51% for the rapidly pyrolyzed char versus 9% for the slowly pyrolyzed one yielding a mineral content of the rapidly-pyrolyzed char of 9 wt%, higher than that of the slowly-pyrolyzed char (5 wt%).

5.4.2.3.3 Pore Size Distributions

The size distribution of pores greater than 1 μm that are of interest in the present study were generated by the digital imaging process described earlier. The macroporosities of the char were obtained by taking the ratio of the measured cross-sectional area of pores and that of char matrix. Rapidly-pyrolyzed char, which was cenospheric, had a large void space in the center and a number of small vesicles distributed throughout the thin wall. The porosities of small vesicles and the large void space, as measured separately, were 0.304 ± 0.103 and 0.696 ± 0.103 , respectively. That the sum of these averaged porosities is 1.00 is fortuitous. The average porosity determined as the complement of the increased char structure is 0.89. The total porosity of slowly-pyrolyzed char was 0.076 ± 0.049 . Fifty particles were examined for each of the two batches. The limited number of sample particles examined are sufficient to show the dramatic difference in porosities of the two char classes.

The pore volume distributions obtained from a stereological analysis is shown in Figure 5.4-9 along with their analytical representations. The area under the curve fit is the

FIGURE 5.4.9 - Pore size distributions of the pyrolyzed char particles. The functional form of the curve fit was $N(r) = A r \exp(B \sqrt{r})$. The area under the curve fit is the overall porosity of the char. The large void space in the center of the char was excluded in obtaining the pore distributions of the rapidly-pyrolyzed char.

overall porosity of the char. The large void space in the center of the char was excluded in obtaining the pore distributions of the rapidly-pyrolyzed char.

The number distribution was fitted with a modified form of Rayleigh distribution. The functional form is

$$N(r) = A r \exp(B \sqrt{r}) \quad (5.105)$$

where r is the radius of pores in micrometers, and A and B are coefficients. The above functional form was adopted because it gave the best curve fit. The coefficients (A , B) that gave the best results from the linear regression for the rapidly-pyrolyzed and slowly-pyrolyzed char were (162.72, -3.12), and (701.99, -4.85), respectively. The curves in Figure 5.4-9 were calculated from the number distributions.

The log mean radii of the pores of the porous shell of the rapidly-pyrolyzed and slowly-pyrolyzed char calculated by the volume weighting were 4.93 and 1.93 μm , respectively. The rapidly pyrolyzed char could be viewed as a cenosphere with a highly porous shell. The porosity in Figure 5.4-9 corresponds to the shell portion only.

5.4.2.3.4 Final Ash Mass Distribution

The two chars yield different ash psd's. Since the density fraction largely eliminates the particle-to-particle variation in mineral content, the final residual ash should be narrowly distributed around $20\text{ }\mu\text{m}$ if all the mineral matter in a coal particle coalesces to form one fly ash. Since the coalescence of mineral matter is limited by many factors, e.g., char fragmentation and mineral matter vaporization, during the combustion, the final fly ash ends up having a wide size distribution ranging from 1 to $15\text{ }\mu\text{m}$. Figure 5.4-10 shows the final ash mass distributions in mass percent obtained from the complete combustion of two samples at 1650 K and 50% O_2 in N_2 .

The distributions are trimodal with two modes in the residual ash range, and one mode in the submicron ash range ($< 1\text{ }\mu\text{m}$) generated by vaporization and recondensation of mineral matter. The percentages of total ash in the submicron mode for rapidly-pyrolyzed and slowly-pyrolyzed char are 46.4 and $32.9\text{ wt}\%$, respectively, for the combustion conditions of high oxygen concentration (50%), and the relatively high concentration of small mineral inclusions of the coals studied. The higher vaporized fraction for the rapidly

FIGURE 5.4-10 - The final ash mass distributions obtained from the two sample chars.

The distributions are trimodal with two modes in residual ash range, and a mode in submicron ash range ($< 1\text{ }\mu\text{m}$). The main difference between the two distributions is that the middle mode from the slowly-pyrolyzed char is narrower, and is shifted to the larger size range.

pyrolyzed char can be explained by the shorter diffusion path for vaporized species in the cenospheric, thin-walled char than in the non-cenospheric, slowly-pyrolyzed char (Quann and Sarofim, 1982).

Both the samples show two modes in their residual ash ($> 1 \mu\text{m}$) mass distributions centered about 3 and 8 μm in aerodynamic diameters, respectively. (The formation of the two modes is explained in detail in Kang et al., 1990). The shapes and locations of the two larger modes are similar for each char with the major difference being in the amounts found in the middle mode. About 74 wt% of the residual ash is found in the middle mode for rapidly-pyrolyzed char whereas only 64 wt% of the residual ash is found in the middle mode for slowly-pyrolyzed char. The middle mode from the rapidly-pyrolyzed char is broader than that from the slowly-pyrolyzed char, and the local maximum of the middle mode is shifted from 2.5 μm for the rapidly-pyrolyzed char to 4 μm for the slowly-pyrolyzed char. The mass mean diameters of the ash from the rapidly-pyrolyzed char and the slowly-pyrolyzed char are 4.20 and 5.09 μm , respectively.

The two ash mass distributions are similar to each other beyond 3 μm . The difference in residual ash distributions is explained as being due to the difference in pore structures. The rapidly-pyrolyzed char has a structure more prone to fragmentation with its wall thickness of approximately 12.5 μm , only one sixth the parent coal diameter. Given that the ash growth is primarily by the coalescence of surface ash particles drawn together or the scavenging of buried mineral matter as the char surface recedes radially during burnout, the thin-walled structure provides a lower chance of ash growth, with a resultant formation of smaller ash particles.

The difference in ash mass distributions resulting from fragmentation is more evident in the middle mode since the larger end of the ash mass distribution is determined mainly by the large mineral inclusions. For a coal particle with a distribution of mineral inclusions, large ash particles of a given size can be produced by coalescence of either a large number of small mineral inclusions or a few fairly large ones. The probability for the latter increases as the ash size gets larger, or as the initial mineral distribution gets broader. In the case of a broad distribution, the larger end of the ash mass distribution is determined by the initial size distribution of the larger end mineral inclusions. Also because of the cube root dependence of size on mass it is less likely to see a size increase for the larger inclusions than the smaller ones.

The experiments were repeated with the Kentucky No. 9 coal following exactly the same procedure but without density separation. Despite the structural differences, the ash mass distributions obtained from samples with and without slow pyrolysis did not show any discernible differences. The combustion experiment carried out with Upper Freeport bituminous coal, a gain without the density separation step, also showed no difference in ash mass distribution. The mineral contents of 63 to 75 μm Kentucky No. 9 and Upper Freeport bituminous coals before density separation were 15.6 and 23.4 wt%, respectively.

This infers that the effect of structural difference in char on the final ash mass distribution becomes significant when the mineral content is lower than a "cutoff" mineral content. The experiments infer that this "cutoff" mineral content lies between 5 and 15 wt%, perhaps closer to 5 wt%. This suggests that in general the effect of char structure (pore structure) on the final ash psd is of second-order importance.

5.4.2.4 Modeling

The experimental results suggest that the size distribution of the large ash particles is determined primarily by that of the large mineral inclusions in the parent coal, modified as appropriate by mineral fragmentation, and is relatively insensitive to changes in pore structure. The major effect of changes in pore structure is on the extent of agglomeration of the smaller mineral inclusions. The extent to which these grow depends upon the relative magnitude of the probabilities for coalescence and of ash particle release. Several models can be used to simulate the competition between these processes. The site lattice percolation model will be used here to qualitatively demonstrate the effect of pore structure. The details of the model are found elsewhere (Kang et al., 1988; Boni et al., 1990). A brief discussion of the model follows.

In the char fragmentation and ash formation model (Boni et al., 1990) a char particle is represented as a cluster of connected occupied sites randomly distributed on a three-dimensional simple cubic lattice. In the cluster two nearest neighbor sites are defined as being connected, with all occupied sites containing an equal fraction of the carbon mass of the initial char particle. The pores, generated randomly as a fraction of the total number of sites, and the environment external to the cluster is defined to be the reactant gases. Pores in this simulation are considered to be macropores, thereby allowing oxygen to penetrate the pore when connectivity of the ambient is established. Reaction is possible only when a given char site is directly in contact with an oxidizing environment, simulating the diffusion controlled regime. Reaction of the char particle is realized by the successive removal of the outermost layer of the char sites. Mineral matter in all cases is distributed among a given fraction of char sites as an initial condition in the simulation. The ash particles on char surface consist of mineral inclusions exposed as the char surface recedes which grow by coalescence as they are drawn together on the shrinking surface and as they intercept included mineral inclusions. The growth process is arrested when char elements, generated by the percolative fragmentation resulting from the growth of the macropores, are consumed. The size to which the ash particles can grow is determined by the macroporosity which determines the size distribution of the char fragments produced.

In order to provide a method of simulating the different types of porosities encountered in char an Ising model was employed which provides a systematic basis for examining the effects of both total porosity and the aggregation of pores. Pores with a size corresponding to a site are initially randomly distributed in numbers sufficient to match the total porosity. A potential is defined as the sum of the reciprocals of the distances of separation of all combinations of pore-pairs. Pores are moved at random and the potential recalculated. The pore is moved only if the potential is increased. The number of times all

pores are moved is designated the number of site visits. For further detail refer to Metropolis et al. (1953), Sevick et al. (1989), and Kang (1991). This procedure is illustrated in Figure 5.4-11 where a two-dimensional char with a macroporosity of 0.3 is represented with random pores and after 4, 8, and 12 visitations, showing the approach to a cenospheric configuration with increasing visitation number. The effect of these changes in pore structure, at a given porosity, is that of broadening the ash size distribution as shown in Figure 5.4-12.

A simple simulation study was performed then on a two-dimensional square lattice with the given experimental data on porosity. Two char particles with porosities of 0.1 and 0.7 were constructed on a 50 x 50 matrix as shown in Figure 5.4-13. The input data were set to simulate the slowly- and rapidly-pyrolyzed chars. The number of site visits for the top left configuration and that for the top right configuration are 1 and 12, respectively, to qualitatively indicate the role of pore structure on mineral inclusions of 1 μm original size

FIGURE 5.4-11 - Snapshots of two-dimensional char with a macroporosity of 0.3 represented in 50 x 50 matrix with random pores (upper left); and after 4 (upper right); 8 (lower left); and 12 (lower right) combinations of adjacent pores.

FIGURE 5.4.12 - Ash mass distributions obtained from ash formation simulation for the two chars in Figure 5.4.11 (upper left and lower right). The two chars have the same macroporosity of 0.3 and same ash content of 0.1 but different pore distributions. The simulation runs show the effect of redistribution of pores on ash mass distributions.

initially randomly distributed on 4.5% of the char sites. The ash psd's, obtained by averaging the results of five runs, are also compared in Figure 5.4-13 and show an increase in mean ash size of a factor of two comparable to the experimentally determined increase of the fine residual ash mode. Although the simulation was two-dimensional, it has previously been shown that the size distribution obtained by a 2-D simulation is close to that obtained by the time-consuming 3-D calculations (Kang 1991). The increase in mean diameter is primarily due to the increase in porosity. At a given porosity, the distribution broadens as the structure is more clustered, which is a clear indication of more coalescence. This enhancement of coalescence is because the receding surface ash particles can travel farther on a char with clustered pores before the char fragments. Given that char samples have the same porosity and mineral content, char with clustered pore sites generates larger ash particles than that with randomly distributed pore sites. The intent here was to semi-quantitatively show how the pore structure influences the distribution of the smaller size inclusions and to provide a method of examining the effects of pore distribution.

5.4.2.5 Practical Implications

The large increase in macropore formation in rapidly-pyrolyzed char resulted in a relatively modest increase in ash mass in the 1 and 3 μm range and in the formation of more sub-micrometer ash. Computer simulations performed on a two-dimensional matrix for

FIGURE 5.4.13 - Snapshots of 50×50 square lattice configurations constructed by following the scheme. The porosity and the number of site visits for the top left configuration are 0.1 and 1, respectively, and those for the top right configuration are 0.7 and 12, respectively. The ash particle size distributions for the two configurations are compared in the lower drawing.

ramified, and clustered char showed similar results indicating that the role of macropores is to reduce the probability of ash coalescence.

The major difference in ash psd between the samples attributed to the structural differences of the parent char is a second order effect since the differences in final ash particle size distributions was not detectable for chars prepared by exactly the same

procedure without the density separation step. For coal density variations of 1.32 to 2.10 (see Figure 5.4-8), the mineral matter content varied from 3.6 to 67.5 wt%, which would yield a variation in final ash size, for a single-ash-per-coal-particle model, of 18 to 51 μm difference which overwhelm those resulting from char structural differences. All these results infer that the effect of structural difference in char is most significant for coals with low mineral content, and less particle-to-particle variation in mineral content.

In conclusion, the macropore structure of a char influences the ash formation process by inducing char fragmentation and by controlling the extent of ash coalescence. But its influence can be observed only when other factors controlling the final distribution are not significantly important. As the particle-to-particle variation of mineral content in coal becomes significant, the final ash mass distribution becomes dominated mainly by that variation (Charon et al., 1990; Barta et al., 1989). As the overall mineral inclusion distribution in coal becomes wide, the final ash mass distribution becomes dominated by the initial mineral distribution (Dunn-Rankin and Kerstein, 1987, 1988). As the coal size distribution becomes wide, the final ash mass distribution becomes dominated by the initial mineral distribution (Kang et al., 1989).

5.4.3 Effect of Alkali Metals on Ash Coalescence

5.4.3.1 Background

A wide size distribution of residual ash particles is the result of the coalescence of mineral inclusions during combustion. Mineral matter forms molten droplets which stay attached to the surface of a burning char. The molten droplets get drawn closer to each other as the char combustion proceeds. When they have high enough surface tension and low enough viscosity, they coalesce. For any significant growth of residual ash to take place the coalescence rate should be so fast that the complete coalescence of all the available mineral impurities can take place within the time scale of char burnout.

The final ash size and composition distributions as well as their structure, therefore, depend on two characteristic time scales: ash coalescence and char reaction time scales. The two time scales can be expressed by the physical and chemical properties of the char and mineral matter.

Coalescence of two touching spherical particles has been studied by many researchers (Frenkel, 1945; Kuczynski et al., 1970; Hiram and Nir, 1983). The coalescence mechanisms are the viscous flow driven by surface tension for the case of molten droplets; and the solid state diffusion for the case of solid droplets. Frenkel derived a simple relationship for the growth of the interface between two spherical particles by viscous flow, which can be written as,

$$x^2 = \frac{3}{2} \frac{\gamma}{\mu} rt \quad (5.106)$$

or

$$t = \frac{2\mu}{3\gamma} r \left(\frac{x}{r} \right)^2 \quad (5.107)$$

where x is the radius of the interface, r the original radius of the sphere, γ the surface tension, μ the viscosity, and t the time for sintering. The relationship can be applied only for early stage of sintering, i.e., $x/r < 0.3$. When we define the coalescence time, t_c , as the time required for x/r to reach 0.3, we find that

$$\tau_c \propto \frac{\mu}{\gamma} r \quad (5.108)$$

The coalescence time, therefore, is proportional to the viscosity and the initial size of ash, and is inversely proportional to the surface tension.

Now let's consider the reaction time scale, t_r . When a particle burns in the external diffusion controlled regime, the char burnout time becomes inversely proportional to the diffusion rate of the gaseous reactant, which is proportional to the reactant concentration, i.e.,

$$\tau_r \propto \frac{1}{D_{O_2} P_{O_2}} \quad (5.109)$$

where D_{O_2} and P_{O_2} are the diffusion coefficients and partial pressure of oxygen, respectively.

Taking the ratio of the two time scales, t_r and t_c , we define a coalescence parameter, $\Lambda_{r/c}$, as,

$$\begin{aligned} \Lambda_{r/c} &= \tau_r / \tau_c \\ &\propto \frac{\gamma}{D_{O_2} P_{O_2} \mu r} \propto \frac{\gamma}{\mu r} \end{aligned} \quad (5.110)$$

This parameter gives basic information on ash coalescence during char burnout. When the coalescence is very fast compared with the char burnout time, i.e., $\Lambda_{r/c} \gg 1$, mineral impurities in a coal particle readily coalesce within the reaction time. On the other hand, if the coalescence time is too long compared with the char burnout time, i.e., $\Lambda_{r/c} \ll 1$, mineral impurities would only partially sinter, resulting in a lacy cluster of spheroidal ash particles.

The ash growth is influenced mainly by the surface tension and the viscosity of the surface ash particles in contact, which in turn are affected by the change of the chemical composition of mineral impurities. The chemical species that can affect the surface tension and viscosity most are the alkali and alkaline earth metals.

The objective of the present study is to investigate the effect of the mineral composition on the structure and size distribution of final ash.

5.4.3.2 Experimental

Combustion experiments were performed in a laboratory-scale laminar flow reactor at MIT with synthetic coals carefully prepared varying the mineral content, and the mineral composition.

5.4.3.2.1 Sample Preparation

Coal has its mineral impurities in two different forms: atomically dispersed mineral matter, and discrete mineral inclusions dispersed randomly throughout coal particles. As an ideal model compound of mineral matter, the material has to be well defined in its dispersity, shape, size and composition.

For the simulation of the atomically dispersed mineral matter, chemicals of desired elements were utilized which are readily soluble to the solvents used for the char preparation. For discrete mineral inclusions, monosized and spherical silica seed particles (Stöber et al., 1968) were generated by a sol-gel technique by mixing a solution of pure alcohol (ethanol) containing a small amount of water and a base catalyst (ammonia) with a silicon alkoxide (tetraethyl orthosilicate, or TEOS) for the study. The concentration of water and ammonia in EtOH was set to produce the maximum size of silica particles ($\sim 0.6 \mu\text{m}$ in diameter). These seed particles were grown further to the desired size by the addition of TEOS solution. The detailed procedure is discussed in the following section.

A solution was made by mixing 340 ml of ethanol (EtOH) with 160 ml of 35% ammonia solution (NH_4OH) in a 2-l Erlenmeyer flask. In the room temperature, 6 ml of TEOS was added to the solution. The solution was stirred moderately throughout the synthesis using a magnetic stirring bar. After 1 to 5 min, the solution became turbid, which is a sign of nucleation of silica embryos. The solution was stirred for 24 hr, after which 100 ml of TEOS-EtOH solution (50/50 by volume) was added. One hundred milliliters of TEOS-EtOH solution was added to the initial solution at eight 24-hr intervals. The time-concentration history of silica growth is shown schematically in Figure 5.4-14 (upper).

In order to maintain the pH of the solution at 10, ammonia solution was replenished to the TEOS-EtOH solution between batches. The final solution was centrifuged and washed several times with EtOH. The final silica particles thus obtained were $1.41 \mu\text{m}$ in diameter. The SEM of the silica particles is shown in Figure 5.4-14 (lower).

C-1718

V-634

FIGURE 5.4.14 - Schematic diagram of time-temperature history of silica growth (upper); scanning electron micrograph of silica particles grown by the method discussed in the text (lower).

Sucrose and carbon black were mixed in a ratio of 2:1 by mass in a beaker. Isopropyl alcohol was added to the beaker. The sucrose-carbon black-isopropyl alcohol slurry was well stirred while heating. Silica particles dispersed in water were added to the slurry. When atomically dispersed mineral impurities had to be simulated, acetates of desired chemical elements (e.g., Na, K, Mg, and Ca) were dissolved in water and were added to the slurry. The slurry was sonicated for 30 min and heated while stirring until it became very viscous. The slurry was then poured into a ceramic boat and put in a pyrolysis oven. The slurry was heated in an inert condition (N_2) in the pyrolysis oven at 250°C for 1 hr followed by at 600°C for 1-1/2 hr. A cake of char was made from the slurry after pyrolysis. The cake was ground and sieved to the desired size ranges (75 to 90 μm and 90 to 106 μm).

Silica particles of size 1.41 μm were used for the char. Calcium acetate and potassium acetate were used to atomically distribute calcium and potassium in the char particles. Table 5.4-3 lists the sample preparation techniques, sample size, and the chemical composition for each of the samples used for the study.

The base material for carbon for the first seven synthetic char samples was sucrose and carbon black (1 to 1 by weight), and that for the last was PFA. The pore size distributions of the two types of char are shown in Figure 5.4-15.

The samples are non-macroporous, and therefore are free from any char fragmentation by macroporosity (Helble and Sarofim, 1987; Kang, et al., 1988).

TABLE 5.4-3. - Synthetic char samples prepared for the study

Sample Number	Size (μm)	ASTM Ash (wt%)	Composition*			Mol % SiO_2 **
			% K	% Ca	% SiO_2	
BA	90/106	3.35	N/A	N/A	N/A	100
KH	90/106	6.65	1.54	—	4.87	67.3
KM	90/106	5.14	0.81	—	4.44	78.1
KL	90/106	4.08	0.312	—	4.10	89.5
CA1	90/106	6.85	—	1.45	3.09	58.7
CA2	90/106	6.03	—	0.90	3.95	74.5
CA3	90/106	6.40	—	0.78	4.99	81.0

*ICP analysis from Galbraith Lab, based on total char weight.
 **Based on ICP analysis.

C-1719

FIGURE 5.4-15 - Pore size distributions of sucrose/carbon black char obtained from mercury porosimetry

5.4.3.2.2 Combustion Experiment

Combustion experiments were carried out with the samples in a laminar flow reactor at MIT. The gas temperature was maintained at 1650 K, and the oxygen concentration was 20%. Details of the reactor can be found elsewhere (Quann et al., 1982). Particle temperature and burnout time were measured with a two-color pyrometer at Northeastern University. The two-color pyrometer had filters with effective wavelengths of 640 and 810 nm. The averages of the measured temperature and burnout time were 2150 ± 71 K and 30 ± 0.8 ms, respectively. Figure 5.4-16 shows an example of the time-temperature history of a char particle. Combustion products were collected on Fluoropore filters, and were analyzed by an SEM and an image analyzer. Primary ash particle size was determined by measuring and averaging the sizes of 500 to 1000 particles. The final ash particle size distribution was also determined using the Andersen Mark II cascade impactor described in Subsection 5.2.3.2.

5.4.3.3 Results and Discussion

Figure 5.4-17 shows the fusion curves of alkali silicates, and the viscosity change of silica with the addition of alkali metals, respectively. The presence of the alkali and alkaline-earth metals lowers the fusion temperature of most of aluminosilicates. They also lower the viscosity of the aluminosilicates by *several* orders of magnitude. The viscosity of a melt is sensitive to its ionic or molecular structure. A great decrease in viscosity with the

FIGURE 5.4-16. - An example of the time-temperature history of a char particle

addition of about 10 mol% of alkali metal oxides (or 20 mol% of alkaline-earth metal oxides) is a manifestation of a major breakdown in the silicate network to a smaller silicate anion groups.

The surface tension of silica increases with the addition of potassium, and decreases with the addition of lithium or sodium. However it does not vary as much as the viscosity. It is therefore mainly by the change of the viscosity that the ash coalescence behavior is dramatically affected by the compositional change of the ash droplets.

Some of the typical ash particles are shown in Figure 5.4-18 after complete combustion of each of the samples. The figures sequentially show the effect of potassium in char on the size and shape of final ash particles produced.

A typical feature of ash from sample BA is that it assumes a randomly shaped clusters comprised of primary particles of the size of initial silica inclusions. The size of the clusters varied from the size of primary particles to that of the parent char particles. Figure 5.4-18 (a) shows a cluster of silica particles from the sample BA. The primary particles of the cluster show no signs of growth, and are loosely attached to each other forming a fragile cluster.

Addition of potassium enhanced the coalescence of these silica particles. Figure 5.4-18 (b) shows final ash particles from the char KL (char with low concentration of potassium). The primary particles vary in size from 1.4 to 6 μm showing partial coalescence, and again forming random clusters. Figure 5.4-18 (c) shows clusters of ash particles from the char KM (char with medium concentration of potassium). The shape and

FIGURE 5.4-17 - Fusion curves of alkali and alkaline-earth silicates (upper) and the viscosity change of silica with alkali metal addition (lower).
From Eitel (1954) (upper) and Paul (1982) (lower).

V-616

(a)

V-635

(b)

FIGURE 5.4-18 - Typical ash particles collected from the combustion of
(a) sample BA and (b) sample KL

(c)

(d)

FIGURE 5.4-18 - Typical ash particles collected from the combustion of
(c) sample KM; and (d) sample KH (continued)

size are very similar to those of silica particles from the sample **KM**. The primary particles ranging from 1.4 to 10 μm have not coalesced completely. About half of the final ash from the char **KM**, however, were non-clustered spheres. Figure 5.4-18 (d) shows spherical particles obtained from the char **KH** (char with high concentration of potassium). Nearly all of the particles examined were spherical and non-clustered.

The primary particle size distributions of all these samples and the volume mean diameter of the primary particles are shown in Figure 5.4-19 (upper) and Figure 5.4-19 (lower), respectively. The size distributions clearly show the increase in the size of the *primary* particles with the increase of potassium in the char matrix.

For each case the coalescence parameter was calculated. The calculation was carried out with the surface tension of 230 dynes/cm (Shartsis and Spinner, 1951), and the viscosity data in Figure 5.4-14. The measured char burnout time was 30 ± 0.8 ms. For the sample **BA** $\Lambda_{r/c}$ was 0.37 (< 1), and for sample **KL** $\Lambda_{r/c}$ was 5.7×10^4 , which was much greater than unity. Samples **KM** and **KH** gave values of the same order as sample **KL**.

According to the calculation, the sample **BA** would not coalesce, and the samples **KH**, **KM**, and **KL** would readily coalesce to form single particles from each of the char samples. The prediction was correct for the samples having composition on the extreme ends, i.e., samples **BA** (no potassium) and **KH** (high in potassium). The two intermediate composition samples - samples **KM** (medium in potassium) and **KL** (low in potassium) - behaved close to the prediction by the coalescence parameter. While this prediction of coalescence by the simple parameter defined in the work is fairly reasonable, the following aspects have to be considered.

Silica particles incorporate potassium into themselves while they recede and scavenge the newly exposed potassium, which was buried in the carbon matrix. However since potassium has a very high vapor pressure at the temperature of the char burnout, most of the potassium vaporizes during the char burnout forming a cloud of potassium vapor. The interaction of the silica particles with potassium becomes limited to what is left in the carbon matrix, and what is vaporized and surrounds the char particle as a cloud. The more the initial content of the potassium is, the more the amount of it left in the char matrix. According to Figure 5.4.14, the amount needed to reduce the viscosity by 4 to 5 orders of magnitude is about 5 mol%. Based on this argument, the amount of potassium incorporated to silica particles of sample **KH** is greater than 5 mol% while that incorporated to silica particles of samples **KM** and **KL** is between 2 and 5 mol%.

The argument above is all based on the assumption that the silica particles on the char surface are thermally in equilibrium. For any given temperature, the transient viscosity of a polymeric melt measured during continuous cooling (heating) of the melt is always lower (higher) than the equilibrium viscosity obtained after holding the melt for some time at the temperature of the measurement. This difference is due to the sluggish rate of structural change in response to the change of temperature. If this relaxation rate is so low that the silica particles do not reach the thermal equilibrium within the char burnout time scale, the

FIGURE 5.4-19 - Cumulative particle size distributions of the *primary* particles (upper); and volume mean particle size change with the composition (lower).

silica particles would behave very differently than those in equilibrium. Hetherington, et al. (1964) showed the above behavior with vitreous silica.

Another point to consider is the degree of mixing of potassium incorporated in the silica network. If the mixing is not complete down to a molecular level, the network breakdown would not be extensive enough to lower the viscosity, and the coalescence behavior would not be predictable with the given equilibrium data. XAFS analysis was attempted for the final ash samples from the four char samples to investigate the interaction of potassium with silica at a molecular level. The analysis, however, was not successful for unknown reasons.

Ash mass distributions were obtained from cascade impactor runs. Results are shown in Figure 5.4-20. Major features of the distributions are 1) that there exist three modes in the ash mass distributions, and 2) that as the potassium content in char increases, the relative strength of the middling mode decreases while the other two increase.

A trimodal distribution of coal ash from cascade impactor runs has often been observed previously during the combustion experiments with most of the project coal samples. The first mode appeared in the submicron range, the second in 2 to 5 μm range, and the third at around 20 μm . The submicron mode is believed to be by the vaporization and recondensation of the more volatile mineral impurities in coal during combustion. The other two modes in the range greater than 1 μm (residual ash modes) are believed to be due to the different extents of coalescence of inclusions during char combustion. The middling mode (2 to 5 μm) is due to the mineral inclusions which have been newly exposed to the char surface and separated from the char by fragmentation before undergoing any significant coalescence with other inclusions. The larger end mode (20 μm) is due to ash particles formed by a significant coalescence between ash particles. The three modes (especially the two residual ash modes) can be observed because ash particles get separated by the char

FIGURE 5.4-20 - Ash mass distributions from cascade impactor runs.

fragmentation before further coalescence. The detailed discussion of the formation of the two residual ash modes (ash > 1 μm) can be found elsewhere (Boni et al., 1990; Kang et al., 1990).

The same trimodal trend is shown here in the cascade impactor runs with microporous chars KL, KM, and KH. The gradual increase of the amount of potassium in char gradually decreases the strength of the middling mode while increasing the strengths of the other two modes manifesting the enhanced coalescence by the presence of potassium.

In the extreme case of no potassium in char (sample BA) only a single peak (the middling mode) appears at 3.5 μm . According to the argument above, this peak is due to the silica inclusions that did not undergo any significant coalescence. As seen in the SEM pictures, however, a typical ash from BA is random clusters of loosely sintered silica inclusions. This indicates that the ash clusters from the sample BA probably has undergone a severe breakdown of the cluster structure into its primary particles. In fact the abrupt changes of the direction of the gas stream flow carrying fly ash particles in a cascade impactor are aerodynamically hostile enough for slightly-sintered clusters to fall apart into individual primary particles (silica inclusions).

In order to verify that the peak at 3.5 μm of sample BA is due mostly to the primary particles from the clusters, a simple calculation for the aerodynamic diameter of the clusters was carried out. The assumptions for the calculation were 1) that 20% of the primary particles of the random clusters are exposed to the surface contributing to the form drag, 2) that the porosity of the random clusters is 30%; and 3) that the Stokes law applies to the particles in the flow field of the cascade impactor, i.e., $F_D = 3 \pi \mu u \sqrt{(S/\pi)}$, where μ , u , and S are the viscosity, the velocity of the gas, and the surface area of the particle in the flow field, respectively. The densities of the silica inclusions, and the char were 2 and 1.2 g/cc, respectively. The diameters of the silica inclusions, and the char particles were 1.4 and 70 μm , respectively. The total number of inclusions in a cluster of ash particles was approximately 4500.

The force balance for a cluster with the Stokes diameter, d_n , in a flow field of velocity u_n is $\rho_n (\pi/6) d_n^3 g = 3 \pi \mu d_n u_n$. The force balance when the skin drag force of a random cluster is assumed to be equal to the sum of the drag forces by 20% of total silica particles of size d_1 and density ρ_1 , $\rho_1 (\pi/6) n d_1^3 g = 3 \pi \mu \sqrt{(0.2 n)} d_1 u_1$. From the two force balances, and setting that $u_1 = u_n$, the Stokes diameter of the random cluster is expressed in terms of the densities of the primary particles and the random clusters, and the diameter of the primary particle as $d_n = \sqrt[4]{(5n) d_1 \sqrt{(\rho_1/\rho_n)}}$. Also from the assumption of 30% porosity, $\sqrt{(\rho_1/\rho_n)} = \sqrt{(1/0.7)} = 1.2$. Therefore the Stokes diameter of the cluster is $d_n = \sqrt[4]{(5 \times 4500) (1.4) (1.2)} = 20.6 \mu\text{m}$. The aerodynamic diameter, therefore, is $d_{n,aero} = \sqrt{2} (20.6) = 29.1 \mu\text{m}$. The calculation shows clearly that a random cluster of silica particles has an aerodynamic diameter greater than 3.5 μm , the diameter observed by a cascade impactor run. Incidentally, the aerodynamic diameter of a 1.4 μm silica inclusion is 1.98 μm . The calculation clearly shows that the single peak observed from sample BA is due to the individual silica inclusions which form the ash clusters.

5.4.3.4 Summary and Conclusion

The role of alkali metals in the formation and the growth of the ash particles has been studied. The viscosities of aluminosilicates are affected by alkali and alkaline earth metals which break down the network of aluminosilicates (network modifiers). Synthetic char samples were prepared from sucrose and carbon black (carbon matrix). Monosized spherical silica particles were included in the synthetic char to simulate discrete mineral inclusions. Potassium, occurring in coal as discrete inclusions (e.g., illites) or as atomically dispersed mineral impurities, has been introduced to the char as a network modifier.

Laboratory-scale experiments with four groups of synthetic chars having silica and varying amount of potassium were carried out. Observations of the collected ash particles under scanning electron microscope showed random clusters of varying size in primary particles, and showed that the increase in potassium in char increases the extent of coalescence between silica particles.

Prediction of the extent of the ash coalescence was attempted by taking the ratio of the ash coalescence time to the char reaction time. Due to the complicated interaction mechanisms of potassium and silica, however, the prediction of the extent of the ash coalescence from the chemical composition was only approximate.

The *residual* ash size distributions of chars with potassium were bimodal while that without potassium was unimodal. The mode in 2 to 5 μm range was due to the silica inclusions which have not undergone any coalescence while the mode around 20 μm is due to ash particles grown by coalescence during combustion.

5.4.4 Effect of Ash Content on Final Ash Distribution

Coal cleaning is essentially a process for the removal of the mineral impurities in coal. One way of studying the effect of coal cleaning is by investigating the effect of ash content in coal on the final ash size distribution.

Six groups of coal samples were prepared from 63/75 μm , Kentucky No. 9 coal (Phase I coal sample) by density separation: coal sample before density separation (baseline coal), coal from 1.36 to 1.40 g/cc, 1.40 to 1.58, 1.58 to 1.70, 1.70 to 2.10, and >2.10 . (Details of the density fractionation are described in Subsection 5.4.2) Each of the coal fractions was burned in the laminar flow reactor at 1650 K and 20 % O_2 in N_2 .

Figure 5.4-21 shows the ash particle size distributions obtained by Malvern size analysis for ash samples generated by combustion of the five density separated coal fractions as well as the baseline coal. Also shown is the size distribution of the minerals by low temperature ashing of the baseline coal. A preliminary comparison of the ash distributions with the mineral distribution, as represented by the low temperature ash, clearly shows that a considerable degree of coalescence has occurred between ash particles for each of the density fractions. (The volume-based median diameters of low temperature ashed ash, ash from the baseline coal, ash from the density fractions of 1.36/1.40, 1.40/1.58, 1.58/1.70, 1.70/2.10, and >2.10 were 6.5, 27, 11, 10, 26, 40, and 50 μm , respectively.)

FIGURE 5.4-21. - Comparison of ash size distributions of Kentucky No. 9 coal samples.

In order to assess the effect of ash content on ash coalescence, the volume-based median diameter of each of the samples was compared with the diameter calculated from the ash content of the coal sample assuming full coalescence as shown in Table 5.4-4. (The ash content of each of the fractions is reported in Figure 5.4-8 of Subsection 5.4.2.) The cube of the ratio of the two diameters (column 4) roughly indicates the extent of ash coalescence. As listed, low density fractions (1.36/1.40 and 1.40/1.58) have low cube ratios indicating relatively low extent of ash coalescence. As the ash content increases, the cube ratio also increases. This is either because the coalescence between ash particles becomes

TABLE 5.4-4. Comparison of diameters of ash generated from combustion of different density fractions of Kentucky #9 coal

Samples	Volume-Based Median Diameter, d_m (μm)	Ash Diameter From Full Coalescence Assumption, d_{fc} (μm)	$\left[\frac{d_m}{d_{fc}} \right]^3$
LTA (minerals)	6.5	-	-
Baseline (ash)	27	30.6	0.68
1.36/1.40 (ash)	11	32.9	0.037
1.40/1.58 (ash)	10	34.8	0.024
1.58/1.70 (ash)	26	49.7	0.143
1.70/2.10 (ash)	40	57.4	0.338
> 2.10 (ash)	50	-	-

more significant for high ash content coal fractions, or because the initial size of mineral inclusions in higher ash content coal fraction is larger than that of inclusions in lower ash content coal fractions. Considering the fact that the coal fractions with density 1.58/1.70 or 1.70/2.10 have densities very close to the average mineral density (2.2 g/cc) these coal fractions would probably have low carbon contents, i.e., are essentially extraneous minerals.

In conclusion, the average ash size increases with increasing ash content of the coal. This is primarily a result of increased mineral coalescence occurring for higher ash content coals.

5.4.5 Continuum Modeling

5.4.5.1 Background

The residual ash produced during char combustion is responsible for problems such as fouling and slagging of heat transfer surfaces in coal fired boilers. Many factors govern the residual ash particle size distribution (PSD): coal PSD (Holve, 1986), mineral matter distribution in coal (Charon et al., 1990; Barta et al., 1990; Wibberley and Wall, 1986), and char fragmentation. As evidenced by the experimental work of Helble and Sarofim (Helble and Sarofim, 1989), and Kang *et al.* (1988), macroporosity in the char can lead to fragmentation which can in turn have an important impact on the final ash size and composition. As an example of the role of fragmentation consider a 50 μm coal particle with 10 wt% of mineral content containing 1 μm monosized mineral inclusions. For the extreme case of massive fragmentation during combustion, about 5000 1- μm particles are generated per coal particle. At the other extreme, in the absence of fragmentation, the mineral matter in the coal completely coalesces to form one 17- μm ash particle per coal particle. Depending on the degree of fragmentation, the final ash particle size and composition distributions can vary between these two extremes given by the distribution encountered in the mineral inclusions and the single particle they form on complete coalescence.

Several models have been proposed on the detailed combustion behavior and its effect on the residual ash formation. Dunn-Rankin and Kerstein (1988) modified the population-balance model (Dunn-Rankin, 1988) of char fragmentation for ash formation assuming that the fragmentation rate of a particle depends on the mass of the particle. Assuming that all surface droplets are subject to removal at a rate that is independent of droplet size, Kerstein (1989) formulated a different population-balance model which takes into account the recession-induced ash movement and coalescence-induced growth. Kang *et al.* (1988) developed an ash release model based on the char percolation model of Kerstein and Edwards (1987). Loehden et al. (1988) developed a model based on the distribution of the organically bound ash on the mineral inclusions, and Monroe (1989) developed a Monte Carlo ash formation model for char cenospheres. In Monroe's model it is assumed that combustion is external diffusion controlled with no char fragmentation; that ash droplets are randomly distributed throughout the char structure with a uniform probability based on char volume; and that any droplets that touch are fused instantaneously into a single well mixed spherical droplets.

The objective of the work is to develop a model which captures the ash coalescence process and does not require a long CPU time. Although the previous model developed in Phase I (Boni et al., 1990) successfully captures the char fragmentation and ash coalescence processes, the model requires a large memory space to represent the char and mineral inclusions with a resolution enough to make the simulation results statistically significant. The model also requires a long CPU time, making the model almost impossible to be employed as a submodel of a fast-running engineering model for mineral matter transformation. In the current continuum model, however, a relatively less CPU-time-, and memory-intensive computer model could be developed by realizing char particles in a continuum space, and by adopting a simpler char fragmentation (or ash separation) process from the char.

5.4.5.2 Model Formulation

5.4.5.2.1 Assumptions

A Monte Carlo model was developed in a continuum space in order to simulate the growth of fly ash particles on a char surface during the char burnout. The model follows the combustion history of a single char particle. The following assumptions are introduced in the model:

1. *Pores considered in the model are those macropores having an effectiveness factor greater than 0.9:* Experimental observation shows that macropores play a vital role on residual ash formation (Helble and Sarofim, 1989; Kang et al., 1988). At a practical combustion temperature of about 2000 K, pores of a 70 μm char through which full access of O_2 is allowed are those greater than 1 μm . The pores of this size range will participate in the oxidation and mainly affect the change of char morphology as the reaction proceeds.
2. *During the recession, a surface ash particle gets separated when it encounters a pore:* Non-macroporous char generates one ash per char whereas macroporous char generates many ash particles per char. This indicates that the separation of surface ash particles is somehow related to the existence of macropores. The connection of the ash separation to the macropores is recognized in the model by this assumption. Oxidation reaction takes place inside macropores being considered in the model. This internal burning undercuts the neck region formed by the char surface and the internal surface of a pore, thereby effecting the separation of the surface ash particle from the char.
3. *No mineral matter vaporizes during the char combustion:* The amount of mineral matter vaporized during char combustion is no more than 5 wt% of the total mineral matter, and therefore does not affect the residual ash particle size distribution (Quann and Sarofim, 1982).

4. *Fragmentation of mineral matter does not affect the residual ash psd over the course of the char combustion:* While some mineral matter (e.g., pyrite, and illite) fragments during combustion, most silicates do not (Raask, 1985). It is these minerals which constitute the bulk of the mineral matter in coal. Pyrite in coal is prevalent but will only fragment under certain conditions.
5. *No ash cenospheres or plerospheres are formed:* Ash cenospheres and plerospheres have been observed by many researchers (Raask, 1968; Fisher et al, 1976; Sarofim et al., 1977). Reports show that the maximum amount of ash cenospheres and plerospheres does not exceed 5 wt% of total ash.
6. *Ash particles remain attached to the receding char surface during char combustion, and are not separated from the char surface by shedding induced by char rotation:* As coal particles begin to devolatilize, gaseous jets of volatiles effusing from the particle give rise to high frequency char particle rotation (Kang, 1987). The surface tension causes ash particles to adhere to the surface of the burning char. Comparing the centrifugal and gravitational forces with the adhesion force, Helble and Sarofim (1989) concluded that at practical combustion conditions the surface tension is high enough to overcome centrifugal force induced by the high frequency rotation of the char.
7. *Mineral inclusions and char are spherical.* Upon contact, two surface ash particles coalesce instantaneously to form one ash particle with the mass of the two particles: The time required for the formation of an effective particle-to-particle bonding by viscous flow as a result of surface tension can be calculated by the Frenkel equation:

$$\frac{x}{r} = 1.225 \sqrt{\frac{\gamma t}{\mu r}} \quad (5.111)$$

where x is the radius of the interface (or the neck), assumed to be circular; t , time; γ , the surface tension; and r , the radius of the spherical particles. The coalescence time of two molten surface ash particles of radius $5 \mu\text{m}$ can be estimated using Eq. (5.111) for an ash surface tension and viscosity of 0.32 N/m and 10^3 N s/m^2 , respectively. The ratio, x/r , which represents the degree of sintering is taken to be 0.3 for the calculation (Raask, 1985; Frenkel, 1948). The calculation thus made shows that the required coalescence time is only a fraction of a millisecond (0.9 ms). This is negligible compared with the total char burnout time of tens of milliseconds, e.g., 90 ms for Montana lignite 90/106 μm at 1350 K, 20% O_2 (Helble and Sarofim, 1989). For high viscosity ashes such as CaO or MgO, coalescence times may be significant.

5.4.5.2.2 Char Representation

A char particle is considered as a sphere of a given radius, R_c , with pores and inclusions of given sizes dispersed randomly. The sizes of each of the pores and the

inclusions, r_p and r_m , are selected to satisfy the desired size distributions. A spherical coordinate system (r, θ, ϕ) is used for the locations of each of the pores and inclusions. Random generation of a location is repeated for each of the inclusions and pores until a non-overlapping arrangement is generated. The distribution scheme is iterated until the desired porosity and mineral content is achieved.

The char reaction is realized by the recession of the char surface normal to itself. The reaction front is defined by the external char surface. At a certain time step, a dispersed phase nearest to the reaction front, whether it be a pore or an inclusion, is located first. Whenever dispersed phase is located, the inclusion(s) is (are) brought onto the surface. For the simplicity of the model, the size of the pores exposed to the char surface is assumed to remain the same. Surface ash particles separate from the body of the char whenever they encounter a pore. As the char surface recedes, the surface ash particles also recede adhered to the surface. Mineral inclusions buried in the char are exposed and the surface concentration of ash particles grows. When the surface ash particles are close enough to touch each other, these particles coalesce to form a larger surface ash particle. The surface ash keeps growing in this fashion until it encounters an internal pore and is separated from the body of the char. For touching coalescence, a check for overlap between surface ash particles is performed every time the reaction front recedes. In order to determine separation of the ash particles, a check for overlap of ash particles with pores is carried out. Those particles overlapping with pores are separated from the carbon and stored in the separated ash bins.

5.4.5.2.3 Data Reduction

Storage bins that increase geometrically in the mass, s , of ash are used. For a minimum size of inclusion equal to 1, the bins used are for mass of 1, 2 to 3, 4 to 7, 8 to 15, 16 to 31, etc.. The representative size of each bin used for the plotting is the geometric mean of the two boundary masses. The number of fly ash particles in bin size s is designated N_s . In order to compare runs at different char dimensions, the number distribution is normalized by the volume of the initial char, i.e., $n_s = N_s / V_{\text{char}}$ where N_s and V_{char} are the absolute number of fly ash particles of size s , and the volume of the initial char, respectively. The reduced number n_s is char-size independent, and is used to describe ash properties in the paper.

5.4.5.3 Parameter for Ash Growth

The ash growth process is a competition between the separation of surface ash from the parent char particle and the coalescence of surface ash particles along with the addition of mineral inclusions to the existing surface ash particles. The competition is a function of two length scales that can represent these two opposing events.

Consider a partially reacted char particle illustrated in Figure 5.4-22 in which pores and mineral inclusions are embedded. The partially grown ash particle on the surface travels along with the receding char surface as the char reaction continues until it encounters a

FIGURE 5.4-22. - Illustration of the formation of a fly ash particle. Open circles and closed circles represent pores and mineral inclusions, respectively. Surface ash particle is also shown as closed circle.

mineral inclusion underneath it. The surface ash grows as the underneath mineral inclusion is added to it. The surface ash particle keeps moving down with the char surface sweeping a volume of the char and scavenging mineral inclusions in the volume until it finally reach an embedded pore. At this instant, the surface ash particle separates from the parent char particle and convects away.

In this scenario, we have two different length scales which are related to the ash growth. One is the coalescence distance, L_c , which is the mean distance a surface ash particle travels until it encounters a mineral inclusion and coalesces with it. The other is the separation distance, L_s , which is the mean distance a surface ash particle travels until it gets separated from the char. As L_c increases, the probability of surface ash growth decreases.

As L_s increases, on the other hand, the probability of a surface ash particle to grow increases. When statistically meaningful expressions for these length scales are obtained, the ratio of these two length scales, $\Lambda = L_s/L_c$, can be a useful parameter to describe surface ash growth. We now derive the two length scales for both planar (semi-infinite slab) and spherical char configurations. The planar configuration analysis can be adopted for swelling coals which, after devolatilization, form thin-shelled cenospheres. For a coal particle maintaining its original, roughly spherical shape, the spherical configuration can be adopted.

5.4.5.3.1 Ash Growth Number in Planar Char

5.4.5.3.1.1 Separation Length Scale, L_s

The separation length scale in a given system is the average distance between pores in the direction of the char recession. Consider a continuum phase in which particles of another phase (α -phase) are randomly distributed (the α -phase is comprised of the pores in a coal matrix in our discussion). For this system, we define a spatial parameter called the *mean free distance*, λ , in the material science literature (Underwood, 1980). The mean free distance is a mean edge-to-edge distance, which represents the uninterrupted inter-a-particle distance through the matrix averaged between all possible pairs of isolated a-particles. The distance can be expressed as follows (Fullman, 1953):

$$\lambda = \frac{1 - (V_v)_\alpha}{N_L} \quad (5.112)$$

where $(V_v)_\alpha$ and N_L are the volume fraction of a-phase, and the number of interceptions of particles per unit length of a test line, respectively. The relation derives from the fact that the number of interceptions with α -particles is the same as the number of interceptions with the matrix. Thus the lineal fraction occupied by the matrix is λN_L , which is also equal to its volume fraction, $1 - (V_v)_\alpha$. The relation is further simplified to

$$\lambda = \bar{L}_3 \frac{1 - (V_v)_\alpha}{(V_v)_\alpha} \quad (5.113)$$

where $\bar{L}_3$ is the mean intercept length (Underwood, 1980). It is the average length of the intercepts when test lines are passed through an a-phase particle at all possible locations and angles. The mean intercept length for mono-sized spheres of radius r is $4r/3$. The separation length scale, L_s , is simply the mean free distance between pores. Assuming uniform pore size, L_s can be expressed in terms of the porosity, ϕ , and the pore radius, r_p , i.e.,

$$L_s = \frac{4}{3} r_p \frac{1 - \phi}{\phi} \quad (5.114)$$

For a given pore volume fraction, the separation distance increases as the pore size increases (or as the number of pores decreases). For a given pore size, the separation distance increases as the porosity decreases. For small porosity, the separation distance can be simplified as follows:

$$L_s \sim \frac{r_p}{\phi} \quad (5.115)$$

5.4.5.3.1.2 Coalescence Length Scale, L_c

The coalescence length scale, L_c , is the distance a surface ash particle travels along with the receding char surface before it collides and coalesces with a mineral inclusion. A collision occurs between a surface ash particle (A) and mineral inclusions (B) whenever the distance between centers becomes as small as d_{AB} ($= r_A + r_B$). Let us imagine a sphere of radius d_{AB} to be circumscribed about the center of A. Whenever the *center* of an inclusion (B) comes within this sphere, B immediately coalesces with A. When a surface ash particle recedes, it sweeps a cylindrical volume of the char the base of which is the projected area of this imaginary sphere on the char surface. The coalescence length scale, L_c , can be obtained by calculating the height of the cylinder which overlaps with one mineral inclusion. An analogy to this analysis is found in the calculation of the mean free path of gas molecules. Consider a cylindrical sweeping volume of height, L_c , with the radius of the base, $2 r_m$. From our definition of the coalescence length scale, the number of centers of (mono-sized) mineral inclusions contained in the cylinder is one, i.e.,

$$\left[\pi (2r_m)^2 L_c \right] \cdot N_v = 1 \quad (5.116)$$

where N_v is the number density of mineral inclusions (i.e., number of inclusions per volume of char). The number density of the mineral inclusions in the above relation is replaced by its volume fraction, θ , using the following relation:

$$\theta = \frac{4}{3} \pi r_m^3 N_v \quad (5.117)$$

From Eqs. (5.116) and (5.117), the coalescence length scale becomes

$$L_c = \frac{r_m}{3\theta} \quad (5.118)$$

Given the inclusion radius, the coalescence length scale increases as the volume fraction, θ , decreases. Given the mineral volume fraction, the coalescence length scale increases as the mineral inclusion size increases. At a fixed mineral volume fraction, the number of inclusions increases as their radius decreases, the distance between inclusions, therefore, decreases and hence the coalescence distance decreases.

From Eqs. (5.114) and (5.118), the parameter for ash growth, Λ , becomes:

$$\Lambda \equiv \frac{L_s}{L_c} = \left[\frac{4r_p}{3} \frac{1-\phi}{\phi} \right] / \left[\frac{r_m}{3\theta} \right] = \frac{4r_p}{r_m} \cdot \frac{1-\phi}{\phi} \cdot \theta \quad (5.119)$$

When the porosity is small, Eq. (5.119) can be simplified to

$$\Lambda = 4 \frac{r_p}{r_m} \cdot \frac{\theta}{\phi} \quad (5.120)$$

Equation (5.120) is composed of two groups. The first is the ratio of the sizes of the pores and the inclusions. The second is the ratio of the volume fractions of the pores and the mineral inclusions. The simple and important physical meaning of the parameter, Λ , is that it gives the average number of mineral inclusions a surface ash particle encounters before it becomes separated. For example, when $\Lambda < 1$, the probability of mineral inclusions to coalesce with each other is small. On the other hand, when $\Lambda \geq 1$, a mineral inclusion on the char surface scavenges Λ mineral inclusions on the average before it separates. The final ash size is, therefore, related to the parameter, Λ .

5.4.5.3.1.3 Transient and Final Ash Size

The same "cylindrical sweeping volume" type of analysis can be carried out again to calculate the surface ash size as a function of time (or degree of conversion). Consider a surface ash particle of radius r_m sweeping down the char volume, and construct a cylinder of height z ($0 \leq z \leq L_s$) and radius $2r_m$. Since all mineral inclusions with their centers in the cylindrical volume coalesce to form one spherical particle of radius r_{ash} , we obtain the following relationship:

$$\frac{4}{3} \pi r_{ash}^3 = \frac{4}{3} \pi r_m^3 \cdot \left[\pi (2r_m)^2 z \right] \cdot N_v \quad (5.121)$$

or

$$r_{\text{ash}} = r_m \left[\frac{z}{L_c} \right]^{1/3} = r_m \Lambda^{1/3} \cdot \left[\frac{z}{L_c} \right]^{1/3} \quad (5.122)$$

From Eq. (5.122), it is found that the average volume of the surface ash increases proportional to the distance the reaction front recedes, i.e., with the degree of conversion. Since the surface ash particle separates after L_s , the surface ash reaches its average final ash size at $z = L_s$. This average final ash size is obtained from Eq. (5.122) as follows:

$$\bar{r}_{\text{ash},f} = r_m \Lambda^{1/3} \quad (5.123)$$

Equations (5.122) and (5.123) actually underestimate the true size. They were derived assuming that the surface ash particle sweeping through the char volume does not grow in size even after incorporating mineral inclusions within the sweeping volume. However, the particle actually grows in size so that the volume swept by the particle (or the number of mineral inclusions the particle scavenges) increases as well. The actual system, therefore, is expected to deviate from the size predicted by Eqs. (5.122) and (5.123) as the reaction depth (or the char size) increases.

The upper bound of the deviation, however, can be predicted by a more rigorous treatment of the growth of the mean ash particle radius. The growth of the ash radius, r_{ash} , can be expressed as

$$\frac{dr_{\text{ash}}^3}{dz} = b(r_{\text{ash}} + 1)^2 \quad (5.124)$$

where b is a constant. Integrating,

$$z = \frac{3}{b} \left[r_{\text{ash}} - 2 \ln \frac{r_{\text{ash}} + 1}{2} - \frac{1}{2} - \frac{1}{r_{\text{ash}} + 1} \right] \quad (5.125)$$

Taking $z = L_s$, this gives $r_{\text{ash}} \sim L_s$ to the leading order in $r_{\text{ash}} \gg 1$. This implies an exponent of unity in Eq. (5.114). Therefore, in the limit of extensive surface ash growth, the surface ash radius will be proportional to Λ .

5.4.5.3.2 Ash Growth Number in Spherical Char

5.4.5.3.2.1 Separation Length Scale, L_s

The main difference between the spherical and planar char configurations is that the continuous increase of reaction front curvature with increasing carbon conversion brings surface ash particles closer to each other. As a result, the coalescence of ash particles is enhanced as the char reaction proceeds. Since the separation length scale is the average edge-to-edge distance between pores in the direction normal to the char surface, the expression for the separation length scale in the planar char configuration also holds in the spherical configuration and Eq. (5.114) can be used as before.

5.4.5.3.2.2 Coalescence Length Scale, L_c

In this section we derive an expression for the coalescence length scale during the early stages of combustion. The coalescence length scale is again defined as the radial distance a surface ash particle moves until it encounters an inclusion. It is obtained from the volume of char whose inclusions coalesce with the sweeping surface ash particle. This volume is no longer cylindrical due to the changing curvature of the reaction front. In the spherical configuration, all surface ash particles move radially towards the center of the char. The volume is a conical piece of a shell of the char which is defined by the projected images of an imaginary sphere.

Consider a char particle in Figure 5.4-23 of radius R_c with mineral inclusions of radius r_m . Suppose after combustion the radius of the char has been reduced to ρ . Define a volume of the char whose mineral inclusions end up being scavenged by the surface ash of radius equal to that of the initial mineral inclusion, r_m and a sweep radius $2 r_m$. Projection of the sphere of radius $2 r_m$ onto the char surface of radius r and the initial char surface of radius R_c produces a conical volume confined in the solid angle defined by the sphere of radius $2 r_m$ and bound by the two caps. The mineral inclusions in the volume end up in the surface ash of initial radius r_m . By checking the number of inclusions in the volume, we can calculate the coalescence distance, L_c .

The volume of the conical piece of the shell, V_c , is obtained by calculating the solid angle of the projected area of an ash particle onto the char surface. It is the volume of the shell times the fraction of the solid angle of the caps. The solid angle of the projected area of a sphere with radius $(2 r_m)$ is $4 \pi r_m^2 / \rho^2$, where ρ is the inner radius of the shell. The volume of the shell is $4/3 \pi (R_c^3 - \rho^3)$. Therefore, the volume, V_c , is

$$V_c = \frac{4}{3} \pi r_m^2 \frac{R_c^3 - \rho^3}{\rho^2} \quad (5.126)$$

FIGURE 5.4-23. - Illustration of the coalescence length scale for spherical char configuration. Char particle with mineral inclusions is shown in 2- (bottom) and 3-dimensional space (top). A surface ash particle (open circle with an asterisk, bottom figure) sweeps a conical volume of the char shell as the char radius decreases from R_c to ρ with progress of the reaction. Mineral inclusions (closed circles, bottom figure) in the volume are incorporated to the sweeping ash particle. Unreacted core of the char is shaded.

Now, by the definition of L_c , there is one inclusion in the volume V_c . Therefore,

$$\begin{aligned}
 1 &= V_c \cdot N_v \\
 &= \frac{R_c^3 - \rho^3}{\rho^2} \cdot \frac{\theta}{r_m} \quad (5.127)
 \end{aligned}$$

The coalescence length, L_c , can be determined by Eq. (5.127) from the relation, $L_c = R_c - \rho$. For $R_c \gg L_c$, the above relation is simplified to

$$L_c = \frac{r_m}{3\theta} \quad (5.128)$$

which is identical to Eq. (5.118) for the planar configuration. The coalescence distance will, of course, vary depending on the position of the surface ash particle being considered. But the limiting expression (Eq. (5.128)) is a useful first approximation.

5.4.5.3.2.3 Ash Growth Number

Equations (5.114) and (5.128) give the same ash growth number as that of the planar configuration:

$$\Lambda = 4 \frac{r_p}{r_m} \cdot \frac{1-\phi}{\phi} \cdot \theta \quad (5.129)$$

Although this is true only for $R_c \gg L_c$, this relation can be used at least for qualitative analysis on the combustion performance and ash formation behavior of coals.

5.4.5.3.2.4 Transient Ash Size

Consider the conical volume of the shell associated with a surface ash particle of radius r_{ash} on the char surface of radius r . Its volume, $V_{c,\rho}$, is,

$$V_{c,\rho} = \frac{4}{3} \pi r_{ash}^3 \frac{R_c^3 - \rho^3}{\rho^2} \quad (5.130)$$

Since all inclusions in the volume $V_{c,\rho}$ end up in the surface ash of radius r_{ash} , assuming conservation of the ash volume yields,

$$r_{ash}^3 = \left[\frac{R_c^3 - \rho^3}{\rho^2} \cdot \frac{r_{ash}^2}{r_m^2} \cdot \frac{\theta}{r_m} \right] r_m^3 = \frac{R_c^3 - \rho^3}{\rho^2} r_{ash}^2 \theta \quad (5.131)$$

Therefore,

$$r_{\text{ash}} = \frac{R_c^3 - \rho^3}{\rho^2} \cdot \theta \quad (5.132)$$

Equation (5.132) is valid only for an intermediate stage of combustion where the growth is mostly due to the scavenging of the mineral inclusions embedded in the char. The stage for this scavenging growth (or the growth by the addition of mineral inclusions to the surface ash particles) is further discussed in the parametric study section.

5.4.5.4 Scaling of the Ash PSD

The self-affine (Vicsek, 1989) nature of the ash mass distributions obtained from simulations at different conditions strongly suggest the possibility of the scaling of the distributions. The scaling approach with the self-affine nature has been adopted by researchers simulating a variety of dynamical processes (Family and Meakin, 1988; Meakin and Family, 1989; Vicsek and Family, 1984; Sahimi and Tsotsis, 1988). Dynamic scaling of droplet growth with homogeneous (Family and Meakin, 1988) and heterogeneous (Meakin and Family, 1989) nucleation was successfully carried out by adopting the scaling concept.

Employing the same concept of scaling, we scale the ash particle size distributions with the ash growth number, Λ . The assumption made for the system is

$$n_s(\Lambda) \sim s^{-\tau} f(s/S(\Lambda)) \quad (5.133)$$

where τ is an exponent that is determined later. The mass mean size increases with the ash growth number, Λ :

$$S(\Lambda) \sim \Lambda^1 \quad (5.134)$$

which is from Eq. (5.123). Now we define the mass density, ρ_m , as the mass of the mineral matter per volume of the system. By definition,

$$\begin{aligned} \rho_m &= \sum s n_s(\Lambda) \\ &\sim \int s^{1-\tau} f(s/S(\Lambda)) ds \\ &\sim S^{2-\tau} \int x^{1-\tau} f(x) dx \\ &\sim \Lambda^{(2-\tau)} \end{aligned} \quad (5.135)$$

where θ is the volume fraction of the mineral matter. To get Eq. (5.136), we assumed that the mineral inclusion size, r_m , is constant. Then, comparing Eq. (5.135) and (5.136), we find

$$2 - \tau = 1 \quad (5.136)$$

or simply, $\tau = 1$. The scaling form, therefore, becomes

$$n_s(\Lambda) \sim s^{-1} f(s/S(\Lambda)) \quad (5.137)$$

The scaling function $f(x)$ is determined by a series of computer simulations. Test of the scaling form in Eq. (5.137) can be done by plotting the scaled quantity $s n_s$ versus the scaled variable $s/S(\Lambda)$. Independent of whether or not Eq. (5.137) is valid, we get one curve of $s n_s$ versus $s/S(\Lambda)$ for different simulation conditions. If Eq. (5.137) is valid, however, these curves for different conditions all collapse into a single curve, the scaling function $f(x)$. The scaled quantity, $s n_s$, is the total mass of ash per initial char volume, m_s . Equation (5.137) implies, therefore, that if the scaling function exists, the ash mass distributions will collapse into a single curve when plotted versus the ash size scaled with the mass mean ash size. The scaling function, if it exists, and the ash growth number can provide qualitatively important information on ash formation during pulverized coal combustion.

5.4.5.5 Simulation Results from Planar Char

A parametric study was performed to compare the Monte Carlo simulation results with the analytical results. The simulation runs were made in a continuum char space having a length, width, and depth of 20, 20, and 200 μm , respectively. For each of the conditions, 20 runs were made and the results of these runs were averaged. The simulation conditions, coalescence length, separation length and their ratio (the ash growth number, Λ) are listed in Table 5.4-5.

To clearly show the effects of the relevant length scales on ash growth, the mineral inclusions and pores were assumed to be monosized. This assumption can be relaxed at will. In Figure 5.4-24 the change of the average surface ash size is plotted versus the reaction depth, z (upper), and the dimensionless reaction depth, z/L_s (lower), for each of the simulation conditions. As is shown in Figure 5.4-24, results of runs at different conditions all collapse into a single curve. The slope of the line in Figure 5.4-24 is $1/3$ as predicted by Eq. (5.122). The results show good agreement between the simulation and the analytical derivation.

The final average ash sizes predicted using the ash growth number, Λ , were compared with those from the simulation, and showed a good agreement. Here, we see the usefulness of the ash growth number, Λ . Given the mineral inclusion size (or its distribution), the mineral content, the pore size (or its distribution), and the pore volume fraction, we can predict the average ash particle size. The size distribution can also be obtained from the scaling argument described earlier.

TABLE 5.4-5. - Input conditions for simulation runs with the model

Run Number	1	2	3	4	5	6	7
Porosity, ϕ_p	0.04	0.08	0.04	0.08	0.04	0.02	0.02
Mineral content, θ_m	0.02	0.04	0.02	0.04	0.04	0.04	0.08
Pore radius, r_p (μm)	2	3	3	4	2	2	2
Mineral radius, r_m (μm)	1	1	1	1	1	1	1
Separation length, L_s (μm)	64	47	97	64	64	132	132
Coalescence length, L_c (μm)	17	8	16	8	8	8	4
Ash growth number Λ (μm)	3.9	5.6	5.8	7.7	7.7	15.9	31.9
<p>a. The dimensions for simulation on a planar char are: length = 20 μm, width = 20 μm, and depth = 200 μm.</p> <p>b. The char radius for simulation on a spherical char is 45 μm.</p>							

The final ash size distributions obtained from each condition were plotted on a log-log scale in terms of number density versus ash size in mass (Figure 5.4-25). The number distributions increase at first with increasing in ash size s at first and then decrease. When plotted in terms of the total mass of ash size s ($s n_s$ or m_s) and the ash size s , the distributions show a clear trend that as the ash number, Λ , increases, the distributions become broader while maintaining similar shapes. In other words, the distribution curves are stretched out to the larger ash size range and pushed down as the ash growth number, Λ , increases. This self-affine nature leads us to the scaling of the distributions discussed earlier. The ash mass distributions were rescaled with the mass mean size of surface ash (which is not much different from the mean mass size of separated ash). The rescaled distributions, indeed, collapse into a single curve as shown in Figure 5.4-25, which is the scaling function $f(x)$. The scaling function is approximately log-normal.

Cenospheric char particles with their wall thickness to radius ratio close to zero can be simulated using the planar char configuration. A typical U.S. coal has about 15 wt% (or ~ 8 vol%) of mineral content. Assuming an average size of mineral inclusions of 1 μm , the coalescence length, L_c , is approximately 4.17 μm from Eq. (5.118). From Eq. (5.122), the wall thickness required for the growth of the surface ash particle to twice the size of the mineral inclusion is $z = 2^3 \times L_c = 2^3 \times (4.17) = 33.4$ μm . Computer simulations of 50 runs was made for a 20 x 20 x 100 μm continuum space, assuming monosized mineral inclusions having a radius of 1 μm . The results are shown in Figure 5.4-26, and agrees well with the calculated value. One thing to notice is that as the reaction depth increases, the average surface ash size from the simulation deviates from the calculated value (the solid line with a slope of unity in Figure 5.4-26). This is due to the breakdown of assumption made when Eq. (5.122) was derived, namely, that the swept volume of the surface ash particle could be treated as being constant. Obviously, the surface ash particles continually increase

FIGURE 5.4-24. - Growth of average surface ash size rescaled with mineral inclusion size (r_{ash}/r_m) with the reaction depth z (upper) and the depth rescaled with the separation length (z/L_f) (lower). Simulation runs were made on a semi-infinite-slab char. Results were replotted based on Eq. (5.122).

FIGURE 5.2-25 - Final ash size distributions. Upper figure shows the ash number density, n_s , versus ash size in mass, s , while the lower figure shows the ash mass versus ash size reduced by the average s/S .

FIGURE 5.4-26 - Growth of the average surface ash radius obtained from the computer simulation of a typical bituminous coal. The line drawn in the lower figure shows the ash mass versus ash size reduced by the average mass s/S .

in size as they coalesce with ash particles released by combustion. This enhances the coalescence between neighboring particles in addition to their rate of incorporation of mineral inclusions.

The ash size distribution on the char surface is also shown in Figure 5.4-27. The largest ash particle obtained after 30 μm of char layer removal was approximately 2.5 μm in radius. The surface ash particle size distributions were scaled using an equation similar to Eq. (5.138):

$$n_s(z) \sim s^{-1} f(s/S(z)) \quad . \quad (5.138)$$

The scaling result is shown in the lower portion of Figure 5.4-27, and shows an interesting feature developing as the reaction proceeds: the magnitude of the peak near $s/S = 1$ slowly decreases while another mode is beginning to develop near $s/S = 0.1$.

5.4.5.6 Simulation Results from Spherical Char

A series of simulations were carried out with spherical char particles to investigate their ash growth behavior. A non-porous, spherical char particle was constructed for the simulations in order to first find out where the major ash growth takes place. Monosized, 1 μm -radius mineral inclusions were distributed randomly throughout a 45- μm -radius char particle, to give a total mineral content of 8 vol%. Ten runs were made for the simulation condition and were averaged to obtain the final data. The mass mean surface ash particle size was plotted in Figure 5.4-28 as a function of the conversion of the char particle. As shown in Figure 5.4-28, the surface ash size grows rapidly in the early stages of conversion. After about 10% conversion, the surface ash size plateaus and subsequently increases rather slowly. As the conversion reaches about 90%, the surface ash size rapidly increases once again and grows to its final size.

In the early stage of conversion, mineral inclusions begin to be exposed to the char surface and form surface ash particles. A small change of curvature by conversion brings these mineral-inclusion-sized surface ash particles close together, and initiates a rapid coalescence among them. This rapid growth continues until it levels off. This can be understood by considering two closely neighboring surface ash particles. Coalescence of two identical surface ash particles to a single particle increases the volume of the final ash particle by a factor of two when it is compared with its parent ash particles. The surface ash radius increase in this case is by a factor of $\sqrt[3]{2}$. In terms of the char surface area occupied by ash particles, on the other hand, coalescence actually reduces the occupied surface area by a factor of $1/\sqrt[3]{2}$. Since the surface area occupied by ash particles is closely related to the degree of coalescence, this reduction of occupied surface area leads to the reduction of the coalescence probability among surface ash particles. The rapid coalescence in the early stage, in other words, results in the surface ash particles growing to larger particles, and at the same time, increasing the distance between them. After growth to a certain size, therefore, the ash particles become far enough apart so that any further major coalescence does not occur for a while.

FIGURE 5.4-27. - Surface ash PSD's obtained from the simulation of a typical bituminous coal of 8 vol% mineral content. Lower portion shows the distributions scaled by the Eq. (5.138). Development of another mode is observed.

FIGURE 5.4-28. - Growth of surface ash with conversion of a non-porous char. The dotted curve is from Eq. (5.131), which accounts only for the growth by addition of mineral inclusions onto a surface ash particle. Initial char radius was $45\ \mu\text{m}$ and the mineral content was 0.08.

In the intermediate stage of conversion, the ash particles grow fairly slowly because the growth is not by coalescence between surface ash particles, but mainly by addition of mineral inclusions to the already existing surface ash particles. As the conversion proceeds, surface ash particles recede along with the receding char surface, scavenging mineral inclusions buried under the surface. This growth by addition of inclusions continues until the ash particles have grown large enough so that major coalescence between surface particles is again possible.

As conversion draws near completion, surface ash particles become close to one another and start to coalesce with one another. This coalescence is mainly due to the rapid change of the char radius of curvature with conversion. The major growth of surface ash particles in the initial and final stages results in an inflection point in the intermediate stage of conversion.

The dotted curve shown in Figure 5.4-28 is from Eq. (5.132), which accounts only for the growth by addition of mineral inclusions to a surface ash particle. Its functional behavior compares with the growth of surface ash in the intermediate stage. A set of computer simulations was carried out with spherical char particles of initial radius of $45\ \mu\text{m}$ in order to answer some of the questions asked for planar configuration. The simulation conditions were the same as those for the simulations in planar configuration as listed in Table 5.4-5. For each condition, results were averaged over ten runs.

As shown in the previous section, the ash growth number, Λ , is an appropriate parameter for the prediction of the average radius (or the degree of ash coalescence) for chars of planar configuration. This may not be necessarily true for the spherical configuration, because the ash growth number does not account for touching coalescence. In order to see the functional dependence of ash size on the ash growth number, the mass mean ash radii of surface ash and separated ash particles were plotted against the ash growth number, Λ . Figure 5.4-29 shows a fluctuation at small Λ , but as Λ increases the ash size increases linearly. The mass mean ash size is about 3 times larger than that predicted for the planar configuration. The trend is again that the mass mean radii of surface ash and separated ash increase approximately with the ash growth number to the one third power, i.e.,

$$\bar{r} \sim \Lambda^{1/3} \quad (5.139)$$

In Figure 5.4-30, the ash mass distributions, m_s , for the seven cases were plotted against the ash size in terms of mass, s . One of the interesting features was that the distributions are bimodal with a peak in the vicinity of $s/S = 0.01$. This is due to the continuous exposure of the mineral inclusions to the char surface and interaction with

FIGURE 5.4-29 - Correlation between the ash growth number and the mass mean radii of separated and surface ash.

FIGURE 5.4-30 - Ash mass distributions from simulations in spherical configuration.

existing surface ash particles by coalescence (Kang et al., 1990). The mass fraction of the peak was about 0.02 with the rest of the mass fraction in the peak next to it. The scaling of the distributions was attempted using the Eq. (5.137). The results are shown in Figure 5.4-30.

5.4.5.7 Conclusion

A Monte Carlo simulation model was developed to study the ash formation process. The model was applied to char of different configurations - spherical and planar chars - in order to assess the effect of the changing curvature of a char with the progression of its reaction.

Analytical expressions were obtained for the ash mass distributions and average ash size by considering a surface ash particle scavenging mineral inclusions in a cylindrical volume of char as its surface recedes. In the course of model development, a dimensionless number called the ash growth number was defined and utilized for further analysis. The ash growth number parameterizes the competition between ash coalescence and char fragmentation. The self-affine nature of the ash mass distributions could lead to a successful scaling of a number of ash mass distributions. The ash growth parameter was used for the scaling. The simulation results showed a bimodality in the ash mass distributions that has been observed in experiments.

The continuum model provides insight concerning the residual ash formation process. It captures most of the qualitative features that are observed from experiments, and has the capability to quantitatively predicting the residual ash particle size distribution.

5.5 Overall Summary and Conclusions

Based on the experimental and modeling work in the vaporization of mineral matter, conclusions can be drawn as follows:

Calcium

- Significant calcium vaporization occurs via finely dispersed calcium only.
- The presence of sulfur slightly inhibits the vaporization of calcium, presumably due to the formation of its sulfide.
- Calcium vaporization occurs via reduction of CaO by CO.
- The CO reduction reaction is in equilibrium above 3500 K and below 2500 K, the reduction kinetics becomes important.

- The calcium partial pressure at the char surface is always below that predicted by equilibrium of the CO reduction reaction due to calcium being present as small inclusions or being non-uniformly distributed or both.

Silicon

- Silicon vaporization is slightly reduced if present as aluminosilicates or if the presence of sodium.
- The presence of sulfur increases silica vaporization, especially at low oxygen concentrations.
- At temperatures below 2500 K and in the absence of sulfur, silicon vaporizes as silicon monoxide and is due to the kinetically limited reaction of CO with silica or silicon carbide.
- At temperatures above 2500 K and in the absence of sulfur, silicon vaporization is as silicon monoxide and is due to the equilibrium of reaction of CO with SiC.

Iron

- Iron vaporization occurs primarily from intrinsic pyrite, not extraneous pyrite.
- Intrinsic pyrite becomes an $\text{Fe}_{1-x}\text{-S}$ melt during char combustion. Iron vaporization from intrinsic pyrite occurs via the vapor pressure of atomic iron over the $\text{Fe}_{1-x}\text{-S}$ melts.
- Iron vaporization is unaffected by the presence of finely distributed calcium.

Conclusions on residual ash formation studies can be drawn as follows:

Beneficiated Coal Study: Gravimelt 7A

- Beneficiation of Kentucky No. 9 coal reduces the relative amount of residual ash, i.e., the fraction of the ash appearing in the submicron fraction increased for the beneficiated coal.
- Beneficiation of swelling Kentucky No. 9 coal changes the char structure. Uncleaned coal formed cenospheric char whereas cleaned coal formed non-cenospheric char.

Effect of Pore Structure

- Macropores induce char fragmentation and limit the coalescence of surface ash particles during char combustion.

- Effect of pore structure on ash mass distribution is significant when the ash content of a coal is lower than 5 wt%.
- Effect of pore structure on ash mass distribution is negligible when the ash content of a coal is greater than 15 wt%.

Effect of Alkali and Alkaline Metals

- Coalescence of ash particles during char combustion is enhanced by the presence of alkali and alkaline earth metals in the coal.
- Prediction of the extent of the ash coalescence is possible by the ratio of the ash coalescence time to the char reaction time.
- Bimodality of the residual ash size distribution is due to the partial coalescence of ash particles caused by either fragmentation or by the coalescence rate being relatively slower than the char reaction rate.

Ash Growth Modeling in Continuum Space

- Analytical expressions were obtained for the ash mass distributions and average ash size by considering a surface ash particle scavenging mineral inclusions as the char reacts.
- A dimensionless number, a ratio of the two length scales relevant to the ash growth process, was derived.
- The dimensionless number, or the ash growth number, was utilized for the parametric studies of the ash growth, and was proved to be potentially useful for the prediction of the ash growth behavior for a given coal of given physical properties.
- The scaling of the ash mass distributions by the ash growth number was possible by the self-affine nature of the distributions.
- The continuum model also predicted the bimodal nature of ash distributions.

5.6 References

- Amdur, M.O., Sarofim, A.F., Neville, M., Quann, R.J., McCarthy, J.F., Elliott, J.F., Lam, H.F., Rogers, A.E., and Conner, M.W. (1986), *Environ. Sci. Tech.*, **20**, 138.
- Anderson Samplers, Inc., Operating manual for Anderson 1 ACFM non-viable ambient particle sizing samplers, February, 1984.
- Arthur, J. (1951), *Transactions of the Faraday Society*, **47**, 164.
- Ayling, A.B. and Smith, I.W. (1972), *Comb. and Flame*, **18**, 173.
- Barta, L.E. Horvath, F. Beér, J.M. and Sarofim, A.F. (1990), Twenty-Third Symposium (International) on Combustion, The Combustion Institute, Pittsburgh, p521.
- Barta, L.E., Vámos, M.A., Toqan, M.A., Teare, J.D., Beér, J.M., and Sarofim, A.F.: Materials Research Society Fall Meeting, Boston (1989).
- Beér, J.M., Boni, A.A., Flagan, R.C., Helble, J.J., Peterson, T.W., Sarofim, A.F., Srinivasachar, S., and Wendt, J.O.L. (1990), Transformations of inorganic coal constituents in combustion systems, DOE report on contract DE-AC22-86PC90751.
- Bellotto, M. (1991), private communications.
- Burgmann, W., Urbain, G., and Frohberg, M.G. (1978), *Mem. Sci. Rev. Met.*, **65**, 572.
- Butler, J.N., and Brokaw, R.S. (1957), *J. Chem. Phys.* **26**, 1636.
- Charon, O. Sarofim, A.F. and Beér, J.M. (1990), *Prog. Energy Combust. Sci.* **16**, 319.
- Chung, T.-H., Lee, L.L., and Starling, K.E. (1984), *Ind. Eng. Chem. Fundam.*, **23**, 8.
- Cleyle, P.J., Caley, W.F., Stewart, I., and Whiteway, S.G. (1984), *Fuel*, **63**.
- Davison, R.L., Natusch, D.F.S., Wallace, J.R., and Evans, C.A., Jr. (1974), *Environ. Sci. Tech.*, **8**, 13.
- Dunn-Rankin, D. (1988), *Combust. Sci. Tech.* **58**, 297.
- Dunn-Rankin, D. and Kerstein, A.R. (1988), *Combust. Flame* **74**, 207.
- Dunn-Rankin, D., and Kerstein, A.R.: *Combust. Flame* **69**, 193 (1987).
- Family, F. and Meakin, P. (1988), *Phys. Rev. Lett.* **61**, 428.

Field, M.A., Gill, D.W. Morgan, B.B., and Hawksley, P.G.W. (1967), Combustion of Pulverized Coal, The British Coal Utilization Research Association, Leatherhead.

Fisher, G.L. Chang, D.P.Y. and Brummer, M. (1976) *Science*, **192**, 553.

Fontijn, A., Kurzius, S.C., and Houghton, J.J. (1973), Fourteenth Symposium (Int.) on Combustion, The Combustion Institute, Pittsburgh, p. 167.

Frenkel, J.J. (1948), *J. Phys. (Moscow)* **9**, 385.

Fullman, R.L. (1953), *Trans. AIME* **197**, 447.

Graham, K.A. (1991), Ph.D. Thesis, MIT Department of Chemical Engineering, Cambridge, MA.

Hansen, F.C. (1959), Approximations for the thermodynamic and transport properties of high temperature air, NASA technical report R-50.

Hastings, T.W. (1984), The effects of thermal processing on lignite char structure and reactivity, Ph.D. Thesis, Department of Chemical Engineering, Massachusetts Institute of Technology.

Haussmann, G., and Kruger, C. (??), A comprehensive kinetics model for CO oxidation during Char Combustion.

Haynes, B.S., Neville, M., Quann, R.J., and Sarofim, A.F. (1982), *J. Coll. Interface Sci.*, **87**, 1.

Helble, J.J., and Sarofim, A. F. (1989), *Combust. Flame*, **76**, 183.

Hetherington, G., Jack, K.H., and Kennedy J.C. (1964), *Phys. Chem. Glasses*, **5**, 130.

Hiram, Y. and Nir, A. (1983), *J. Colloid Interface Sci.*, **95**, 462.

Holve, D.J. (1986), *Combust. Sci. and Tech.* **44**, 269.

Huggins, F.E., Huffman, G.P., Shah, N., Jenkins, R.G., Lytle, F.W., and Greegor, R.B. (1988), *Fuel*, **67**.

Kang, S.-G. Kerstein, A.R. Helble, J.J. and Sarofim, A.F. (1990), *Aerosol Sci. Tech.* **13**, 401.

Kang, S.-G., Charon, O., Sarofim, A.F., and Beér, J.M.: Sixth Annual International Pittsburgh Coal Conference, Pittsburgh (1989).

Kang, S.-G. Helble, J.J. Sarofim, A.F. and Beér, J.M. (1988) Twenty-Second Symposium (International) on Combustion, The Combustion Institute, Pittsburgh, p231.

Kang, S.-G. (1991), Ph.D. Thesis, MIT Department of Chemical Engineering, Cambridge, MA.

Kang, S.W. (1987), Ph.D. Thesis, Department of Mechanical Engineering, M.I.T.

Kerstein, A.R. (1989), Combust. Flame **77**, 187.

Kerstein, A.R. and Edwards, B.F. (1987), Chem. Eng. Sci. **42**, 1629.

Kuczynski, G.C. (1949), Trans. AIMME, **185**, 169.

Kuczynski, G.C., Neuville, B., and Toner, H.P. (1970), J. Appl. Polym. Sci., **14**, 2069.

Levasseur, A.A., Goetz, G.J., Lao, T.C., and Patel, R.L., submitted for publication.

Lewis, G.N., Plume opacity investigation at a stoker-fired plant, Meeting of the Western States Section of the Combustion Institute, April, 1987.

Liu, B.Y.H., Pui, D.Y.H., and Rubow, K.L., from Aerosols in the Mining and Industrial Work Environments, Volume 3, Instrumentation (Marple, V.A. and Liu, B.Y.H., eds.), Chapter 70, Characteristics of Air Sampling Media, Ann Arbor Science Publishers, Michigan, 1983.

Loehden, D. Walsh, P.M. Sayre, A.N. Beér, J.M. and Sarofim, A.F. (1988) Engineering Foundation Conference on Mineral Matter and Ash Deposition from Coal, Engineering Foundation, p279.

Markowski, G.R.: Aerosol Sci. Tech. **7**, 127 (1987).

Markstein, G.H. (1963), Ninth Symposium (Int.) on Combustion, The Combustion Institute, Pittsburgh, p. 137.

McElroy, M.W., Carr, R.C., Ensor, D.S., and Markowski, G.R. (1982), Science, **215**, 13.

Meakin, P. and Family, F. (1989), J. Phys. A: Math Gen. **22**, L225.

Metropolis, N., Rosenbluth, A.W., Rosenbluth, M.N., and Teller, A.H.: J. Chem. Phys. **21**, 1087 (1953).

Mitchell, R.E. (1988), Twenty-Second Symposium (Int.) on Combustion, The Combustion Institute, p. 69.

Monroe, L.S. (1989) PhD. Thesis, Department of Chemical Engineering, M.I.T..

National Air Pollution Control Board (1969), Air Quality Criteria for Particulate Matter, United States Dept. of Health, Education, and Welfare, National Air Pollution Control Board, Pub. No. AP-49, Washington, D.C.

Neville, M., and Sarofim, A.F. (1982), Nineteenth Symposium (Int.) on Combustion, The Combustion Institute, Pittsburgh.

Nusselt, W. (1924), Z. Ver. dt. Ing., **68**, 124.

Otterbein, M., and Bonnetain, L. (1968), Carbon, **6**, 877.

Ozturk, B., and Fruehan, R.J. (1985), Met. Trans. B, **16**, 801.

Paul, A. (1982), Chemistry of Glasses, p82, Chapman and Hall, New York, NY.

Powell, R.W., Ho, C.Y., and Liley, P.E. (1966), Thermal Conductivity of Selected Materials, NSRDS-NBS 8, National Bureau of Standards.

Quann, R.J. (1982), Ash vaporization under simulated pulverized coal combustion conditions, Sc.D. Thesis, Department of Chemical Engineering, Massachusetts Institute of Technology.

Quann, R.J., Neville, M., Janghorbani, M., Mims, C.A., and Sarofim, A.F. (1982), Env. Sci. Tech., **16**, 776.

Quann, R.J. and Sarofim, A.F. (1982), Nineteenth Symposium (Int.) on Combustion, the Combustion Institute, Pittsburgh, p. 1429.

Raask, E. (1968) J. Inst. Fuel, **43**, 339.

Raask, E. Mineral Impurities in Coal Combustion, Hemisphere, Washington, 1985.

Radovic, L.R., Walker, P.L., and Jenkins, R.G. (1983), Fuel, **62**, 209.

Reid, R.C., Prausnitz, J.M., and Poling, B.E. (1987), The Properties of Gases and Liquids, 4th Edition., McGraw-Hill Book Company.

Rossberg, M.Z. (1956), Elektrochem, **60**, 952.

Sahimi, M. and Tsotsis, T.T. (1988), Chem. Eng. Sci. **43**, 113.

Sarofim, A.F. Howard, J.B. Padia, A.S. (1977), Combust. Sci. Tech. **16**, 187.

Satterfield, C.N. (1970), Mass Transfer in Heterogeneous Catalysis, Robert E. Krieger Publishing Co., Malabar, FL.

Schwerdtfeger, K. (1966), Trans. of Met. Soc. of AIME, 236, 1152.

Senior, C.L., and Flagan, R.C. (1984), Twentieth Symposium (Int.) on Combustion, The Combustion Institute, Pittsburgh.

Sevick, E.M., Monson, P.A., and Ottino, J.M.: Chem. Eng. Sci. 44, 21 (1989).

Shartsis, L., and Spinner, S. (1951), J. Research NBS, 46, 385.

Smoot, D.L. and Smith, P.J. (1985), Coal Combustion and Gasification, Plenum, New York.

Spalding, D.B. (1953), J. Inst. Fuel, 26, 289.

Stöber, W., Fink, A., and Bohn, E. (1968), J. Colloid Interface Sci., 26, 62.

Stull, D.R., and Prophet, H., JANAF Thermochemical Tables, second edition, NSRDS-NBS 37, National Bureau of Standards, June, 1971.

Timothy, L.D., Sarofim, A.F., and Beér, J.M. (1982), Nineteenth Symposium (Int.) on Combustion, the Combustion Institute, Pittsburgh, p. 1123.

Tognotti, L., Longwell, J.P., and Sarofim, A.F. (1989), The products of the oxidation and combustion of a single char particle in an electrodynamic balance, submitted for publication.

Turkdogan, E.T., Kor, G.J.W., and Fruehan, R.J. (1980), Ironmaking and Steelmaking, 6, 268.

Twomey, S.: J. Comput. Phys. 18, 188 (1975).

Underwood, E.E. (1980), Quantitative Stereology, Addison-Wesley, Reading, MA.

Vicsek, T. (1989), Fractal Growth Phenomena, World Scientific, Singapore.

Vicsek, T. and Family, F. (1984), Phys. Rev. Lett. 52, 1669.

Waters, B.J., Squires, R.G., and Laurendeau, N.M. (1988a), Comb. and Flame, 74, 91.

Waters, B.J., Squires, R.G., and Laurendeau, N.M. (1988b), Comb. Sci. and Tech., 62, 187.

Wibberley, L.J. and Wall, T.F. (1986), Combust. Sci. and Tech. 48, 177.

Wicksell, D.D.: Biometrika 17, 84 (1925).

Zygourakis, K. and Glass, M.: Chem. Eng. Comm. 70, 39 (1988).

**DATE
FILMED**

8 / 3 / 93

END