AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

DOE/ER/45249--T2

Summary Report of Research Accomplishments

Z. A. Munir

Department of Mechanical, Aeronautical, and Materials Engineering

University of California, Davis

Davis, CA 95616-5294

Submitted to: Dr. Alan Dragoo
Office of Basic Energy Sciences
Department of Energy
Washington, D.C. 20550

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

April 1992

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Table of Contents

1.	INTRODUCTION	1
2.	SUMMARY OF RESEARCH (COMBUSTION SYNTHESIS)	1
2.1	THEORETICAL INVESTIGATIONS	1
2.1.1	<i>Pore formation During Combustion Synthesis</i>	1
2.1.2	<i>SHS Diagrams</i>	3
2.1.3	<i>Theoretical Analysis of Refractory Nitride Synthesis</i>	5
2.2	MECHANISTIC INVESTIGATIONS	7
2.2.1	<i>The Synthesis of Simple Compounds</i>	7
2.2.2	<i>Synthesis of Composites and Solid Solutions</i>	12
2.3	MODEL COMBUSTION STUDIES	16
2.4	REVIEW PAPERS	18
3.	LIST OF PUBLICATIONS	19
3.1	PUBLICATIONS ON COMBUSTION SYNTHESIS (COPIES IN APPENDIX)	19
3.2	REPRESENTATIVE PUBLICATIONS FROM PRIOR DOE SUPPORTED RESEARCH	21
4.	APPENDIX	23
4.1	REPRINTS OF PUBLICATIONS (ITEM 3.1 ABOVE)	23
4.2	NEW JOURNAL ANNOUNCEMENT	23

1. INTRODUCTION

This report summarizes research accomplished with the financial support of the Office of Basic Energy Sciences (OBES) of the Department of Energy. The more recent work, that dealing with the field of Combustion Synthesis, is summarized in this report. The earlier work, dealing with sintering and the role of surface reactions, is referred to by way of a list of representative publications. Since the details of all of these accomplishments are amply described in journal and book publications, only a brief summary of each is given under the appropriate category. Copies of all of the publications resulting from research supported by OBES are attached in the Appendix.

2. SUMMARY OF RESEARCH (COMBUSTION SYNTHESIS)

2.1 THEORETICAL INVESTIGATIONS

2.1.1 *Pore formation During Combustion Synthesis*

We have conducted a theoretical analysis of the contribution of thermal migration to the formation of pores in combustion-synthesized materials. Because of the large (typically $10^5 - 10^6$ K·cm⁻¹) temperature gradients encountered in self-propagating combustion synthesis reaction, an uneven distribution of vacancies can result (the Soret effect). The flux of any component in the presence of concentration and temperature gradients is expressed as

$$J = -D\left(\frac{\partial C}{\partial x}\right) - \frac{DCQ_t}{RT^2}\left(\frac{\partial T}{\partial x}\right) \quad (1)$$

where D is the diffusivity of the component, C is its concentration, Q_t is the heat of transport, T is temperature, R is the gas constant, and x is the direction of the mass-transport. We have provided the first analysis of the role of the thermal migration in the formation of porosity in the products of combustion synthesis. On the basis of simplifying geometry, the geometric width (ΔX) of the void formed by thermal migration is calculated as

Figure 1. The calculated pore diameter/particle size ratios for cases of T_H + (a) 1500 K, (b) 2000 K, and (c) 2500 K, all with $Q_d = 60 \text{ kcal} \cdot \text{mol}^{-1}$ and $Q_i = 100 \text{ kcal} \cdot \text{mol}^{-1}$.

$$\Delta X = \frac{\Delta t}{R} \cdot Q_i \frac{dT}{dx} \left[\frac{D_H}{T_H^2} - \frac{D_c}{T_c^2} \right] \quad (2)$$

where Δt is the duration of the thermal gradient, dT/dx is the temperature gradient, D_H and D_c are the diffusivities at the high (T_H) and low (T_c) temperature ends of the gradient, and the other symbols are as defined above. Our analysis shows that thermal migration can contribute significantly to the porosity of the product as seen in Figure 1. For example, as is shown in Figure 1(c), for a temperature gradient of $10^6 \text{ K} \cdot \text{cm}^{-1}$ and a combustion temperature and velocity of 2500 K and $1 \text{ cm} \cdot \text{s}^{-1}$, respectively, the ratio of the pore to the diameter of the particle is about 25%. Details of these analyses and their results were published: a copy of the paper is included in the Appendix. This analysis is the first of its kind and provides a basic understanding of the formation of porosity in combustion synthesized materials.

2.1.2 SHS Diagrams

We have introduced the concept of SHS diagrams and provided a theoretical basis for its development. The basis of our theoretical analysis is the Zeldovich relationship

$$v_a/v_m = (e)^{1/2} \quad (3)$$

where v_a and v_m are the maximum (adiabatic) and the minimum velocities of a propagating combustion wave. The minimum velocity represents the value just before the wave is extinguished. Combining Eq. (3) with the dependence of velocity on temperature and utilizing simplifying assumption, we derived the following parameter:

$$F = \frac{q_2}{q_1} \left(\frac{T_1}{T_2} \right)^2 \exp \left[-\frac{E}{R} \left(\frac{1}{T_1} - \frac{1}{T_2} \right) \right] \quad (4)$$

where q_1 and q_2 are the enthalpies of the reactions at the maximum (T_1) and minimum (T_2) temperature at which a self-sustaining wave is possible. In Eq. (4) E is the activation energy for the combustion process and R is the gas constant. The enthalpies can be related by the amount of diluent needed to change T_1 to T_2 . Thus, according to Eq. (3), the condition $F = e$ describes a boundary between the existence of self-propagating (SHS) reactions and the absence of such reactions.

We have conducted experimental work to determine the validity of our theoretical model of this boundary and to compare our analysis with those of other theoretical investigations. An ideal SHS diagram is depicted in Figure 2(a) and one containing derived boundaries and experimental results is shown in Figure 2(b). The experimental results agree well with our theoretical predictions for the case of 398 kJ·mol where the assumed activation energy is based on the diffusion of the reactants through a product layer. In Figure 2(a) we show two other boundaries: steady-state SHS/non-steady state SHS and SHS/thermal explosion (TE). Although we did not provide theoretical

Figure 2(a). An "ideal" SHS diagram.

Figure 2(b). Theoretical SHS diagram.
proposal\doc\final.rpt

analyses for these boundaries, we did provide experimental results for the steady-state SHS/non-steady state SHS. The experimental configuration used in the experimental portion of this research employed the arrangement of functionally gradient materials (FGM).

2.1.3 Theoretical Analysis of Refractory Nitride Synthesis

An important distinction of nitride synthesis and other similar gas-solid reactions is the need to provide for direct gas access through existing porosity in the reacting solid. We have provided a mathematical analysis for the role of porosity in the synthesis of refractory nitrides, and, by implication, other materials prepared by gas-solid combustion reactions. Permeation of the gas is not an important factor in synthesis if the required nitrogen is already residing in existing pores. We have shown that under such conditions, the degree of conversion to the nitride, C , is

$$C = \frac{1}{S} \left[P_{N_2} \cdot \frac{\epsilon}{1-\epsilon} \cdot \frac{V_m}{RT} \right] = 1 \quad (5)$$

where S is the stoichiometric ratio of the nitride, P_{N_2} is the pressure of the nitrogen gas, ϵ is the porosity of the reactant metal powder, V_m is the molar volume of the metal, and R and T have their usual meaning. Examples of calculations based on this theoretical analysis are shown in Figure 3. These results show that relatively high gas pressures are needed to ensure that all of the required nitrogen is present in the existing pores. We have generalized this approach to provide a relationship showing the relative importance of permeation in the synthesis of nitride. Modification of Eq. (5), by setting $C = 1$, gives

$$P_{N_2} = \frac{S(1-\epsilon)}{\epsilon} \cdot \frac{RT}{V_m} \quad (6)$$

Figure 3. The dependence of the degree of conversion to nitrides on P_{N_2} for selected elements. $T = 1500\text{ K}$; $\epsilon = 0.7$.

Figure 4. A generalized relationship between P_{N_2} and the molar volume of elements with useful nitrides at complete conversion to the appropriate nitride phase. $T = 1500\text{ K}$; $\epsilon = 0.5$. Nitride phases: A, M_3N_4 ; B, MN; C, M_3N_4 ; D, M_2N .

Figure 4 shows the relationship between P_{N_2} and V_m for four stoichiometric groups of refractory nitrides. It is seen, for example, that the synthesis of the nitrides of Hf and Zr is much less affected by the problem of permeation of the gas than, for example, the synthesis of Cr and B nitrides.

2.2 MECHANISTIC INVESTIGATIONS

The aim of this part of the research is to understand the nature of the combustion synthesis process for a variety of important ceramic, metallic, and composite materials. Research was carried out to investigate the mechanism of synthesis in simple (nitrides and silicides), composite ($TiC + Ni_3Al$), and solid solution materials (TiN_xC_y). Investigations were also conducted on the role of particle size in the mechanism of synthesis of titanium silicide. The important contributions from these investigations are described briefly under the appropriate rubric.

2.2.1 *The Synthesis of Simple Compounds*

Although investigations were made on the mechanism of a variety of materials (TiN, NbN, MoSi₂, and nickel silicides) the bulk of the effort in this phase of our research has been focused on the synthesis of titanium nitride. We have demonstrated that the passage of the combustion wave results only in the formation of a thin layer of the nitride on the surface of the Ti particles. Since, however, in the presence of the unsaturated titanium, TiN is thermodynamically unstable, the next step involves the dissolution of nitrogen (after the dissociation of TiN) into the titanium. The step terminates when the titanium is saturated with nitrogen and the nitride phase nucleates again. This process is shown by the results presented in Figure 5. The sharp peak in Figure 5(b) and at right in Figure 5(a) represents the nitrogen concentration associated with the location of the wave at the point when it was quenched in liquid argon. Behind the wave, the concentration of nitrogen is significantly lower and is consistent with that of a solid solution of N in Ti. As the distance from the

Figure 5. (a) Concentration profile along the surface of a quenched, partially-reacted Ti sample. (b) Concentration profile in the vicinity of the quenched reaction front.

quenched wave increases (moving toward the left in Figure 5) the nitrogen concentration increases up to the level of the nitride. Visual observations of the quenched-sample are consistent with the microprobe analyses. The quenched wave appears in the form of a faint golden ring followed by a gray region which gradually changes color, becoming golden as the distance from the wave increases. Titanium nitride has the distinctive golden color.

We have carried out calculations to ensure that the proposed mechanism is consistent with theory. The essence of these calculations is the demonstration that the time needed for the dissolution of nitrogen is consistent with the experimental observations. The latter is determined from measurement of the wave velocity and the distance behind the quenched wave to the point where the nitride phase has reformed on the surface. The time required to redissolve the nitride phase is

$$t = 0.6 \frac{r^2}{D} \quad (7)$$

where r is the radius of the titanium particle and D is the diffusion coefficient of nitrogen in titanium. The incorporation of the maximum amount of nitrogen in the titanium particle is related to the ratio of the nitride surface-layer thickness to particle radius, ξ/r , by

$$(\xi/r)_c = 1/2 \left[\left(1 + \frac{4}{3} \frac{C_m}{C_x} \right)^{1/2} - 1 \right] \quad (8)$$

where C_m and C_x are the concentrations of nitrogen in the metal at the solubility limit and in the nitride (TiN), respectively. These values are obtained from the Ti-N phase diagram at the combustion temperature. For typical particle sizes of Ti of $r = 5 \mu\text{m}$, we calculate $t = 0.8 \text{ s}$, which is appreciably less than the time needed for the wave to move across the gray region (behind the wave), $\sim 4 \text{ s}$. These calculations, along with the microprobe and X-ray analyses, provide support of the proposed mechanism of synthesis of TiN by a self-propagating combustion method.

Other investigations on the mechanism of combustion synthesis included studies on the influence of nitrogen pressure, initial porosity, and amount of diluent on the synthesis of TiN. From the dependence of the combustion wave velocity on temperature, i.e.,

$$v^2 = \frac{f(n)C_p D_t}{q} \cdot K_o \frac{RT_c^2}{E} \exp(-E/RT_c) \quad (9)$$

where $f(n)$ is a function of the kinetic order, n , of the reaction, C_p is the heat capacity of the product, D_t is the thermal diffusivity, q is the heat of the reaction, R is the gas constant, T_c is the combustion temperature, K_o is a constant, and E is the activation energy of the process. From the dependence of v on T_c , shown in Figure 6, an activation energy of $342 \pm 50 \text{ kJ} \cdot \text{mol}^{-1}$ was calculated. This value is in good agreement with reported activation energies for the diffusion of N in TiN. The influence of porosity of the Ti reactant on the combustion synthesis of TiN was investigated. It was shown, as seen in Figure 7, that the porosity influences the degree of conversion to the nitride. The maximum conversion is obtained at an intermediate relative density; higher densities gave, expectedly, lower conversion because of the limited gas permeation. On the opposite end, at low relative densities, it was shown that the low conversion is a consequence of the melting of the titanium.

The effect of porosity is also manifested by the spatial distribution of the product phases (Figure 8) and by the stoichiometry of the resulting nitride phase. The latter is shown in Figure 9 as the amount of TiN_{1-x} as a function of amount of diluent for surface and bulk locations in the

Figure 6. Temperature dependence of the combustion velocity of diluted and undiluted samples of Ti.

Figure 7. Effect of relative density on the conversion to the nitride (conversion is based on the assumption that the product is stoichiometric TiN).

Figure 8. Spatial distribution of the amount of titanium and the lattice parameter, αTiN_{1-x} , of the product TiN in combusted samples (ρ is relative density).

product. It was shown that the complete conversion to the stoichiometric nitride takes place when the diluent is at a level of 40% or higher.

The influence of particle dispersion on the mechanism of the combustion synthesis of titanium silicide, Ti_3Si_3 , was also investigated. It was demonstrated that two types of reactions are possible: a solid-state reaction involving interdiffusion, and a liquid-phase reaction. The former was found to

Figure 9. Effect of diluent level on the relative amount of the total TiN_{1-x} in the product and its departure from stoichiometry.

be dominant with small Ti particles and low heating rates. As the particle size increases, the dominance changes from solid-state to liquid-phase reactions. Microstructural and X-ray analyses provided an understanding of the sequence of steps in the formation of this silicide. The synthesis of Ti_5Si_3 goes through the sequence $\text{TiS}_2 \rightarrow \text{TiSi} \rightarrow \text{Ti}_5\text{Si}_4 \rightarrow \text{Ti}_5\text{Si}_3$.

2.2.2 Synthesis of Composites and Solid Solutions

We have investigated the mechanisms of synthesis of a ceramic-metal composite ($\text{TiC} - \text{Ni}_2/\text{Al}_3$) and a solid solution (TiC/Ni_y). In the first investigation the goal was to determine the relationship between the microstructure of the end composite and the experimental parameters of synthesis. Among these parameters were the initial metal/ceramic and Al/Ni ratios, as well as the level of pressure applied during synthesis. Unless the ratio of Al/Ni exceeded that needed for the formation of NiAl_3 , no Ti-Al alloy formed and the product contained TiC plus the appropriate Ni-Al "compound" according to the binary diagram of these metals, as shown in Table 1. Nearly fully dense

(>99%) TiC-Ni/Al composites can be synthesized with a dependence of the final porosity on the applied uniaxial pressure as shown in Figure 10. A more interesting finding is the dependence of the grain size of the ceramic phase (TiC) on the metallic content of the composite, Figure 11. Relatively small TiC grains can be formed in a composite containing a metal content of ≥ 40 wt%. An example of the microstructure of nearly fully-dense (porosity <1%) 50 wt% TiC - 50 wt% NiAl which was synthesized under a pressure of 20.7 MPa. The relatively round and well dispersed TiC grains are about 2 μm in size. This composite had a microhardness of 1111 $\text{kg}\cdot\text{mm}^{-2}$. The dependence of the grain size of the ceramic phase on the metallic content of the composite is consistent with the trend in the combustion temperature as determined by the amount of metal in the product. Higher metallic contents result in lower combustion temperature such that grain growth (of the ceramic) is diminished. In addition, higher metallic contents give rise to longer diffusion fields for the TiC grains and hence lower rates of grain growth.

Figure 10. Residual porosity for samples containing both () (Ni + Al) and () (3Ni + Al) as the binder combusted under various pressures.

Figure 11. TiC grain size of samples containing varying amounts of () (Ni + Al) and () (3Ni + Al) at the binder combusted under 20.7 MPa (3000 psi).

The formation, in one step, of a solid solution of TiC-TiN was demonstrated by another investigation. The result is a homogeneous TiC_xN_y phase having the cubic NaCl structure. It was established that the mechanism of formation of this solid solution involves first the formation of the non-stoichiometric carbide phase, TiC_x , followed by the incorporation of nitrogen atoms in the vacant carbon sites. Thermodynamic calculations show (see Figure 12) that the carbide phase is stable (relative to TiN) above about 1960 K. Experimental results (combustion temperature and nitrogen pressure) shown in a calculated TiC-TiN phase stability diagram (Figure 13) demonstrate the consistency of the observed mechanism with thermodynamic calculations.

Figure 12. Standard free energy of formation of TiC and TiN as a function of temperature [48].

Figure 13. Stability regions for TiN and TiC at different pressures and temperatures.

2.3 MODEL COMBUSTION STUDIES

In modeling and related theoretical analyses of the self-propagating combustion synthesis, two assumptions have been widely invoked: (a) that no reaction takes place ahead of the advancing wave, and (b) that the melting of one of the reactants is a prerequisite to the propagation of the combustion wave. Experimental substantiation of these assumptions using the typical mixed powder reactants is difficult, if not impossible. Not only do such reactions suffer from surface impurity contributions, but more importantly, the use of powders gives rise to an ill-defined reaction interface. To alleviate some of these difficulties we have designed and carried out experiments in which the reactants are foils.

Using the Ni-Al system, we investigated the mechanism of synthesis of nickel aluminides using foil ensembles embedded in a "chemical oven," as shown schematically in Figure 14. Using this novel experimental approach, a combustion wave can be propagated along the foil ensemble parallel to the direction of the Al-Ni interfaces. By providing an inert medium (Al_2O_3) at one end of the ensemble, we are able to quench the reaction front for subsequent analysis. Figure 15 shows the microstructure of a quenched sample. Behind the combustion front, the product is the homogeneous NiAl alloy and ahead of the front is clear evidence of significant interaction. Microanalysis of the phases formed

Figure 14. (a) Representation of the use of a chemical oven. (b) The use of an inert layer to arrest the propagation of the reaction.

Figure 15. Microstructure of a region near a front whose progress was arrested by the presence of an invert layer. Sample with initial composition: Al + Ni.

ahead of the wave showed the formation of several Ni-Al phases in the expected distribution relative to the remaining portion of the original Ni foils. All of the aluminum has reacted. This is obviously a clear indication of the invalidity of the first assumption in the modeling studies discussed above. What is also interesting about the formation of these pre-combustion reactions is their agreement with the reported phase equilibria for these two metals. A remarkable example of this is shown in Figure 16 where the clearly visible boundary in microstructure represents the transition from a region containing Al_3Ni and Al (lower portion) to a region containing Al_3Ni_2 , Al_3Ni , and Al. This boundary (located ahead of the quenched wave) represents the formation of Al_3Ni through a peritectic reaction at 854°C . The correspondence of phases present in the product of combustion synthesis with equilibrium diagrams has been reported by others and is believed to occur in systems in which a liquid phase is formed during the reaction.

Figure 16. Boundary between regions at relatively large and intermediate distances ahead of the front in a quenched sample.

Finally, the second assumed criteria for the propagation of a combustion wave (that the propagation of the wave takes place when one of the reactants melts) was found not to apply in the case of the Ni-Al foils experiments discussed above. Not only is there clear evidence of melting ahead of the quenched wave, but also measurements of the ignition temperatures of foils with varying compositions showed that this is not a valid assumption. Figure 17 shows that the ignition temperature is relatively constant with composition (for four Ni-Al "compounds") and it corresponds closely with the melting point of Ni.

2.4 REVIEW PAPERS

Two major review articles were written in response to invitations from two journals: *Ceramic Bulletin* and *Materials Science Reports*. The first review published in 1988 is eight pages long and contains 90 references. The second, more comprehensive review (published in 1989) is 87 pages long and contains 262 references. Both reviews have been widely cited and referenced as sources for

Figure 17. The dependence of the combustion temperature on composition.

details on combustion synthesis. The second review was the basis of a workshop sponsored by the National Science Foundation on this topic. Because of these review articles and others whose results are described above, the Principal Investigator has been invited to give lectures at international and national meetings and seminars in the US and abroad. These activities and the continuing research effort in this field have been the primary reasons for the establishment of the *Journal of Materials Synthesis and Processing* with the Principal Investigator acting as Co-Editor (see the attached Call for Papers).

3. LIST OF PUBLICATIONS

3.1 PUBLICATIONS ON COMBUSTION SYNTHESIS (COPIES IN APPENDIX)

1. The Combustion Synthesis of Refractory Nitrides: Part I, Theoretical Analysis, Z. A. Munir and J. B. Holt, *Journal of Materials Science* 22:710 (1987).
2. Thermodynamic Consideration of the Formation of Refractory Nitrides by Combustion Synthesis, Z. A. Munir and J. B. Holt, in *Materials Processing by Self-Propagating High-Temperature Synthesis*, K. A. Gabriel et al. (eds.), p. 1, 1987.

- 3a. Synthesis of High Temperature Materials by Self-Propagating Combustion Methods, Z. A. Munir, *Ceramic Bulletin* 67:342 (1988) (Invited Review Paper).
- 3b. Also published in the *Chinese Journal of Powder Metallurgy Technology* 67:1 (1988).
4. The Interaction Between Titanium and Nitrogen Under Conditions of Combustion and Low Heating Rates, S. Deevi and Z. A. Munir, in *Proceedings of High Temperature Materials Chemistry Symposium IV*, The Electrochemical Society, Honolulu, HI, October 1987, ECS Proceedings Volume 88-5, p. 623, 1988.
5. The Synthesis of Titanium Nitride by a Self-Sustaining Combustion Method, Z. A. Munir, S. Deevi, and M. Eslamloo-Grami, *High Temperatures, High Pressures* 20:19 (1988).
6. Reactivity of Powders During the Combustion Synthesis of Metallic and Ceramic Phases, Z. A. Munir, in *Proceedings of International Symposium on the Science and Technology of Sintering*, Tokyo, November 1987, (Invited Paper), S. Somiya et al. (eds.), Elsevier Science Publishers, p. 528, 1988.
7. Gas-Solid Reactions Under a Self-Propagating Combustion Mode, S. D. Dunmead, Z. A. Munir, and J. B. Holt, *Solid State Ionics* 32/33:474 (1989).
8. Self-Propagating Exothermic Reactions: The Synthesis of High Temperature Materials by Combustion, Z. A. Munir and U. Anselmi-Tamburini, *Materials Science Reports* 3:277 (1989) (Invited Review Paper).
9. The Propagation of Solid-State Combustion Wave in Ni-Al Foils, U. Anselmi-Tamburini and Z. A. Munir, *Journal of Applied Physics* 66:5039 (1989).
10. The Effect of Porosity on the Combustion Synthesis of Titanium Nitride, M. Eslamloo-Grami and Z. A. Munir, *Journal of the American Ceramic Society* 73(5):1235-39 (1990).
11. The Effect of Particle Dispersion on the Mechanism of Combustion Synthesis of Titanium Silicide, J. Trambukis and Z. A. Munir, *Journal of the American Ceramic Society* 73(5):1240-45 (1990).
12. The Contribution of Thermal Migration to Pore Formation During SHS Reactions, Z. A. Munir and L. L. Wang, in *Proceedings of the First US-Japanese Workshop on Combustion Synthesis*, Y. Kaieda and J. B. Holt (eds.), National Research Institute for Metals, Tokyo, Japan, pp. 123-37, 1990.
13. Observations on the Combustion Reactions Between Thin Foils of Nickel-Aluminum, U. Anselmi-Tamburini and Z. A. Munir, in *Combustion and Plasma Synthesis of High Temperature Materials*, Z. A. Munir and J. B. Holt (eds.), VCH Publishers, New York, NY, 1990.
14. Combustion Synthesis in the TiC-Ni-Al System, S. D. Dunmead, Z. A. Munir, J. B. Holt, and D. D. Kingman, in *Combustion and Plasma Synthesis of High Temperature Materials*, Z. A. Munir and J. B. Holt (eds.), VCH Publishers, New York, NY, 1990.

15. The Effect of Nitrogen Pressure and Diluent Content on the Combustion Synthesis of TiN, M. Eslamloo-Grami and Z. A. Munir, *Journal of the American Ceramic Society* 73(8):2222-27 (1990).
16. Theoretical Predictions of the SHS/Non-SHS Boundary and the Establishment of "SHS Diagrams", N. Sata and Z. A. Munir, in *Proceedings of the Symposium on High-Temperature Materials Chemistry V*, W. B. Johnson and R. A. Rapp (eds.), The Electrochemical Society, Proceedings Volume 90-18, pp. 99-105, 1990.
- 17a. The Mechanism of Synthesis of High Temperature Materials by Combustion Processes, Z. A. Munir, *High Temperature Science* 27:279-93 (1990).
- 17b. Also published in *Materials Chemistry at High Temperatures*, Vol. 2, Processing and Performance, John W. Hastie (ed.), Humana Press, Clifton, NY, pp. 279-93, 1990.
18. The Mechanism of Synthesis of Titanium Nitride by Self-Sustaining Reactions, S. Deevi and Z. A. Munir, *Journal of Materials Research* 5(10):2177-83 (1990).
- 19a. The Preparation of Multi-Phase Materials Through Self-Propagating Powder Reactions, Z. A. Munir, in *Sintering of Multiphase Metal and Ceramic Systems*, G. S. Upadhyaya (ed.), Sci-Tech Publications, c/o Gower Publishing Co., Brookfield, VT, 1990.
- 19b. Also published in *Solid State Phenomena* 8&9:37-46 (1989).
20. Simultaneous Synthesis and Densification of TiC/Ni-Al Composites, S. D. Dunmead, Z. A. Munir, J. B. Holt, and D. D. Kingman, *Journal of Materials Science* 26:2410-16 (1990).
21. The Combustion Synthesis of Refractory Nitrides: Part II, The Synthesis of Niobium Nitride, S. Zhang and Z. A. Munir, *Journal of Materials Science* 26:3380-85 (1991).
22. Synthesis of Molybdenum Silicides by the Self-Propagating Combustion Method, S. Zhang and Z. A. Munir, *Journal of Materials Science* 26:3685-88 (1991).
23. Spin Combustion in the System Nickel-Silicon, S. Zhang and Z. A. Munir, *Journal of Materials Science*, in press.

3.2 REPRESENTATIVE PUBLICATIONS FROM PRIOR DOE SUPPORTED RESEARCH

1. A Consideration of the Role of Sintering in Gas-Solid Interactions, Z. A. Munir, *Thermochimica Acta* 48:91-97 (1981).
2. Surface Oxide and Sintering of Metals, Z. A. Munir, *Powder Metallurgy* 4:177-80 (1991).
3. The Thermal Decomposition of Cadmium and Cobalt Carbonates, Z. A. Munir and J. L. Rice, *High Temperature Science* 14:171-80 (1981).
4. The Oxidation-Reduction Kinetics of Palladium Powder, Z. A. Munir and P. G. Coombs, *Metallurgical Transactions B* 14B:95-99 (1983).

5. A Theoretical Analysis of the Stability of Surface Oxides During the Diffusion Welding of Metals, Z. A. Munir, *Welding Journal (Research Supplement)* 62:333s-36s (1983).
6. The Decomposition of Cadmium Carbonate in Air and in Vacuum, B. J. Asirvatham and Z. A. Munir, *Journal of Materials Science* 21:1997 (1986).
7. Particle Evolution During the Decomposition of CdCO_3 , Z. A. Munir and B. J. Asirvatham, *Journal of Materials Science* 21:2002 (1986).

4. APPENDIX

4.1 REPRINTS OF PUBLICATIONS (ITEM 3.1 ABOVE)

4.2 NEW JOURNAL ANNOUNCEMENT

**DATE
FILMED**

7 / 27 / 93

END