DOE/CE/23810-11B

**MEASUREMENT OF VISCOSITY, DENSITY
AND GAS SOLUBILITY OF REFRIGERANT BLENDS**

RECEIVED

JUN 10 1993

OSTI

Quarterly Progress Report

1 January 1993 - 31 March 1993

**Ricard C. Cavestri, Ph.D.
Jens Munk MSEE**

**Imagination Resources, Inc.
5130 Blazer Memorial Parkway
Dublin, Ohio 43017**

April 1993

**Prepared for
The Air-Conditioning and Refrigeration Technology Institute
Under
ARTI MCLR Project Number 655-51400:Blends**

This project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.67% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.33% of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institute, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyright covering this paper.

Abstract

Liquid/liquid miscibilities of four different 32 ISO VG polyolesters and one alkylbenzene at three concentrations were determined. Also a full vapor lubricant equilibrium (VLE) viscosity reduction of a 32 ISO VG mineral oil with HCFC-22 is complete. Partial viscosity reduction information by the fractionate components from R-502 in 32 ISO VG mineral oil is presented from 40°C (104°C) and 70°C (158°F) isotherms.

Contents

1 Scope	1
1.1 Statement and Chemical Properties of Lubricants	1
2 Significant Results	3
2.1 Miscibility Determinations	3
2.2 Viscosity Measurements	4
2.3 Viscosity of Mineral Oil and HCFC-22	4
2.4 Viscosity of Mineral Oil and HCFC-502	4
Compliance with agreement	5
Principal Investigator Effort	5
A Registered Trademarks of Suppliers	6
B Miscibility of Refrigerant Blends with Polyolesters	8
C Viscosity and Solubility of HCFC-22 with 32 ISO Mineral Oil	15
D Viscosity and Solubility of HCFC-502 with 32 ISO Mineral Oil	21

List of Figures

B.1	Miscibility of HFC-32/HFC-125/HFC-134a/HC-290 (30/55/20/5), with Polyolesters	9
B.2	Miscibility of HFC-32/HFC-125 (60/40), with Polyolesters	10
B.3	Miscibility of HFC-32/HFC-134a (30/70) with Polyolesters	11
B.4	Miscibility of HFC-32/HFC-125/HFC-134a (30/10/60) with Polyolesters . .	12
B.5	Miscibility of HFC-125/HFC-143a (45/55) Polyolesters	13
B.6	Miscibility of HFC-125/HFC-143a/HFC-134a (44/52/4) Polyolesters	14
C.1	Viscosity of 32 ISO VG Mineral Oil with HCFC-22	16
C.2	125°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	17
C.3	100°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	17
C.4	80°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	18
C.5	60°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	18
C.6	40°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	19
C.7	20°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	19
C.8	0°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	20
C.9	-20°C Isothermal Viscosity, Pressure and Solubility of 32 ISO VG Mineral Oil with HCFC-22	20
D.1	40°C Isothermal Viscosity, Pressure and Total Gas Solubility of 32 ISO VG Mineral Oil with R-502 Azeotrope	22

D.2 70°C Isothermal Viscosity, Pressure and Total Gas Solubility of 32 ISO VG Mineral Oil with R-502 Azeotrope	22
---	----

List of Tables

A.1 Registered Trademarks of Suppliers	7
--	---

Chapter 1

Scope

The purpose of this study is to measure the viscosity, density and solubility of four refrigerant mixtures using a single polyolester lubricant. The same measurements will be performed on the individual gases that make up the refrigerant mixtures. The refrigerant mixtures are for blends A, B, C and D respectively, HFC-32/HFC-125 (60/40), HFC-32/HFC-134a (30/70), HFC-32/HFC-125/HFC-134a (30/10/60), and HFC-125/HFC-143a/HFC-134a (44/54/2). The lubricant used in this evaluation is a fully miscible 32 ISO VG branched acid polyolester. Solubility information will include the ratio of fractionation of the individual gases.

A base line evaluation of HCFC-22 and R-502 in a 32 ISO VG mineral oil is included so that a comparison of viscosity and density fluid properties can be determined

1.1 Statement and Chemical Properties of Lubricants

Lubricants used in this program are proprietary, thus rather than being specific, a generic nomenclature is used. It can be assumed that all of the polyolesters used in this program are pentaerythritol esters. The most effective method of reporting lubricant quality is to determine alcohol type and stoichiometry of carboxylic acids used in the synthesis. The amount of complexing that was used to provide the viscosity and liquid miscibility of the product with the various refrigerants should also be reported.

Unfortunately, due to proprietary concerns, only the miscibility and viscosity differences of a polyolester are reported. Specific structural properties of the polyolester remain with the manufacturer.

The table A.1, placed at the beginning of the report, identifies trademarks, registered

trademarks or copyrighted names of lubricants used.

Chapter 2

Significant Results

2.1 Miscibility Determinations

Four different polyolesters and one alkylbenzene were examined, at three different refrigerant/lubricant concentrations, and the temperatures of liquid/liquid immiscibility were determined (Appendix B). Alkylbenzene was introduced into the examination only to examine the aromatic properties toward miscibility. Surprisingly, for blend D a lower temperatures partial miscibility was observed. This suggests a potential for good oil return and inverse miscibility at the higher temperatures, indicating undiluted hydrocarbon lubrication is possible.

Lubricant B, a 32 ISO VG branched acid polyolester, was found to be the most generally miscible. Lubricant C was of similar viscosity but determined to be the least miscible. Lubricants A and D are in the intermediate range of miscibility, making them potential candidates for this study.

Lubricant B was chosen for this study since it represented a polyolester of very high liquid/liquid miscibility and is assumed to have very little influence on the fractionation of the various single gasses that make up the refrigerant blends. One of the objectives of this research is to study the mixed gas vapor solubility behavior at various pressures and temperatures. Fluids showing levels of immiscibility may dramatically impact the fractionation of individual gasses at different temperatures and pressures.

2.2 Viscosity Measurements

Viscosity measurements are performed at isothermal temperatures with varying pressure in an oscillating body viscometer. Fluid properties of viscosity, density and solubility are determined simultaneously. Solubility of single and mixed gasses are determined each time viscosity and density data points are taken. The viscometer is also a very accurate densitometer, allowing it to be used in monitoring the consistency of the fluid.

When refrigerant blends are used, the vapor space of the viscometer is maintained to equal the gas composition of the pure refrigerant blend. The fractionation of the mixed gasses is determined at every temperature and pressure. Samples of the fluid/refrigerant mixture are taken to determine the percent refrigerant by weight in the fluid. The ratio of gasses are determined by gas chromatography.

2.3 Viscosity of Mineral Oil and HCFC-22

Appendix C details the isothermal viscosity, density and solubility of HCFC-22 in 32 ISO VG mineral oil. The temperature of the viscosity determinations stop at -20°C . Attempts to measure the viscosity at a -40°C were unsuccessful, since the fluid became immiscible for refrigerant concentration greater than 9%.

2.4 Viscosity of Mineral Oil and HCFC-502

Appendix D details 40°C and 70°C temperatures of R-502 isothermal viscosity determinations. Purge gas was maintained at the R-502 azeotrope ratio. Percent concentration of refrigerant represents total of both gasses that were soluble in the fluid at that pressure and temperature.

Compliance with Agreement

Imagination Resources, Inc. has complied with the statement of the contract.

Principal Investigator Effort

The principal investigators have devoted 270 hours toward the completion of this contract. Activities have gone toward responding and reporting early refrigerant miscibility information and presenting data to the Technical Oversight Group. Experimental facilities are being established for improved productivity. Technical personnel have spent 480 hours.

Appendix A

Registered Trademarks of Suppliers

**THE SYNTHETIC LUBRICANTS USED IN THIS TESTING PROGRAM ARE
REGISTERED TRADEMARKS, TRADEMARKS, OR ARE NONE OF THE RESPECTIVE MANUFACTURER**

Table A - 1

Fluid	Name	Manufacturer	Type	Registered Trademark, Trademark, or None
A	Iceomatic SW32	Castrol	Branched Acid Polyolester	Registered Trademark
B	Emery 2927a	Henkel, Emery Group	Branched Acid Polyolester	Registered Trademark
C	RL - 184	ICI Chemicals and Polymers, Ltd.	Mixed - Acid Polyolester	Registered Trademark
D	Artic EAL 224R	Mobil	Mixed - Acid Polyolester	Registered Trademark
E	Shrieve Zerol 150	Shrieve Chemical Company	Mineral Oil	Registered Trademark
F	Sun ISO 3GS	Witco, Corporation	Mineral oil	Registered Trademark

Note: All fluids are 32 ISO VG viscosity.

Appendix B

Miscibility of Refrigerant Blends with Polyolesters

Miscibility of Refrigerant Mixture

HFC-32(30%), HFC-125(55%), HFC-134a(20%), and HC-290(5%)

Miscibility of Refrigerant Mixture

HFC-32(60%) and HFC-125(40%)

Miscibility of Refrigerant Mixture

HFC-32(30%) and HFC-134a(70%)

Miscibility of Refrigerant Mixture

HFC-32(30%), HFC-125(10%), and HFC-134a(60%)

Miscibility of Refrigerant Mixture

HFC-125(45%) and HFC-143a(55%)

Miscibility of Refrigerant Mixture

HFC-125(44%), HFC-143a(52%) and HFC-134a(4%)

Appendix C

Viscosity and Solubility of HCFC-22 with 32 ISO Mineral Oil

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at 125 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at 100 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

**Viscosity and Solubility of 32 ISO VG Mineral Oil
Determined at 80 °C w/ HCFC-22**

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

**Viscosity and Solubility of 32 ISO VG Mineral Oil
Determined at 60 °C w/ HCFC-22**

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at 40 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at 20 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at 0 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Viscosity and Solubility of 32 ISO VG Mineral Oil Determined at -20 °C w/ HCFC-22

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

Appendix D

Viscosity and Solubility of R-502 with 32 ISO Mineral Oil

**Viscosity and Solubility of 32 ISO VG Mineral Oil
Determined at 40°C w/ Blend HCFC-502**

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

**Viscosity and Solubility of 32 ISO VG Mineral Oil
Determined at 70°C w/ Blend HCFC-502**

Viscosity via Gas Solubility Equilibrium
Oil degassed to 20 Millitorr

END

DATE
FILMED

6 / 30 / 93