EXTENT OF DAMAGE TO MELT FRONT
FUNCTION OF ENERGY OF PULSED LASER IRRADIATION

J. Narayan and C. V. White

Solid State Div., Oak Ridge National Laboratory, Oak Ridge, TN 37830

ABSTRACT

The depth of melt front penetration induced by Q-switched ruby laser irradiation has been studied by electron microscopy for laser pulses of different duration and energy density in thermally diffused and ion implanted silicon. In thermally diffused specimens, dissolution of dislocation loops and precipitates by the laser radiation provides evidence for melting and the depth over which loops and precipitates are dissolved provides a measure of the melt front penetration depth. In ion implanted specimens, if the melt front does not exceed the thickness of the implanted layer, dislocation tangles and polycrystalline regions are observed after the laser irradiation. A complete annealing of displacement damage is achieved at an energy density (threshold) where the melt front penetrates beyond the damage layer.

INTRODUCTION

It has been recently reported¹ that high power laser pulses can be used to remove displacement damage in ion implanted silicon much more efficiently than can be achieved by conventional thermal annealing in a furnace. The purpose of the present work is to show that the laser pulses lead to melting in phosphorous diffused and ion implanted silicon and that a certain threshold in the energy density of the laser pulse is needed to remove the displacement damage completely in ion implanted silicon. This threshold in energy density for a complete annealing of displacement damage corresponds to the situation where the melt front exceeds the thickness of the damage layer.

EXPERIMENTAL

Silicon single crystals of <100> orientation (Czechralski grown, 500 μ m thick) used in this investigation were obtained from Monsanto. Diffusion of phosphorous was carried out in a furnace at 1100°C for 60 minutes using PH₃ gas, and the crystals were then slowly cooled to room temperature. Boron (¹¹B, 35 keV) implantations were carried out on 80 Ω -cm, n-type, FZ specimens; phosphorous (³¹P 80 keV) and arsenic (⁷⁵As, 100 keV) implantations were done on 10 Ω -cm, p-type, FZ specimens. A vacuum of about 2 x 10⁻⁶ Torr was maintained in the implantation chamber². The doses of implanted ions varied from 10¹⁴ to 2 x 10¹⁶ ions cm⁻²; the temperature of the specimens remained near 25°C during the implantation. The laser annealing of thermally diffused and ion implanted specimens was accomplished with pulses from a ruby (λ = 0.694 μ m)₃ laser, operated in a Q-switched mode with pulse duration 20 or 50 x 10⁻⁹ secs (n secs). The energy density of the laser pulses was varied from 0.6 to 3.0 Joules cm⁻². Our measurements of energy density are subject to 10 - 15% uncertainty.

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability for the accuracy, completeness, or usefulness of the information disclosed herein, or represents that its use would not infringe upon privately owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

149

The irradiated specimens were thinned chemically from the back side while masking the front surface. The thickness of the laser-annealed regions was determined by stereoscopic techniques and thickness fringes using transmission electron microscopy.

RESULTS AND DISCUSSION

After the thermal diffusion treatment, the silicon specimens contained dislocation loops and phosphorous precipitates. Small clusters with black-white directions under dynamical diffraction conditions always parallel to the diffraction vectors (see Fig. 1) were identified as precipitates; larger images with double-arc contrast were due to dislocation loops. The average precipitate size and number density were determined to be $120\text{\AA}$ and $3.0 \times 10^{15} \text{ cm}^{-3}$ respectively. The average size of the dislocation loops was found to be $200\text{\AA}$ with a number density of $1.0 \times 10^{15} \text{ cm}^{-3}$; uncertainties in the sizes and number densities were 10%. From stereomicroscopy it was determined that the loops and precipitates were approximately uniformly distributed from the surface to a depth of about $1.0\mu\text{m}$. The precipitates exhibited strain contrast corresponding to compression centers, as expected for phosphorous precipitates. The dislocation loops were determined to be of interstitial type.

Fig. 1. Bright-field electron micrograph of phosphorous diffused specimen taken under dynamical diffraction conditions showing annealed defect-free regions $0.29\mu\text{m}$ deep produced by one pulse of 1.5 cm^2 , $\tau = 50 \text{ n sec}$.

Fig. 1 is a bright-field (with dynamical diffraction conditions) electron micrograph of a phosphorous diffused specimen which was irradiated with one 50 n sec. pulse of energy density 1.5 J cm^{-2} . One pulse produced an annealed, defect-free (containing no phosphorous precipitates and dislocation loops) region $0.29 \mu\text{m}$ thick. The thickness of the annealed region was measured by stereomicroscopy and could also be directly estimated from the number of thickness fringes because the microscope sample was wedge-shaped near the edge. The extent of the defect and precipitate free region was $0.38 \mu\text{m}$ after two such pulses; and was $0.58 \mu\text{m}$ after seven pulses. A saturation phenomenon in the thickness of the annealed region was observed after approximately five pulses. The results of 1.5 J cm^{-2} , 50 n sec pulses are summarized in Table I.

Table I. Ruby Laser ($\lambda = 0.694 \mu\text{m}$) Annealing Parameters in Phosphorous Diffused silicon.

Pulse Energy Density $E(\text{Joule cm}^{-2})$	Pulse Duration (Nano secs)	Number of Pulses	Depth of Annealing (μm)
1.5	50	1	0.29
1.5	50	2	0.38
1.5	50	5	0.56
1.5	50	7	0.58
2.0	20	1	0.57
2.0	20	3	0.70
2.0	20	5	0.75
2.0	20	14	0.77
3.0	20	1	0.95

The thickness of the annealed regions were similarly determined for 1, 3, 5 and 14 laser pulses of energy density 2.0 J cm^{-2} and pulse duration 20 n sec and the results are also summarized in Table I. Again saturation in the annealing depth was observed after about five laser pulses. It should be mentioned that in the specimens irradiated with three or more laser pulses, a small amount of reprecipitation of phosphorous near the surface was observed. This is probably related to the segregation coefficient of phosphorous in silicon being slightly less than unity. For 2.0 and 3.0 J cm^{-2} (20 n sec) laser pulses, the increase in the annealing depth (from $0.57 \mu\text{m}$ to $0.95 \mu\text{m}$) is approximately proportional to the pulse energy density. A complete annealing of defects up to a depth of one micron was possible with one pulse of $E = 3.3 \text{ J cm}^{-2}$ and $\tau = 20 \text{ n sec}$.

The formation of a liquid layer during laser irradiation is the most plausible mechanism to account for the dissolution of precipitates and dislocation loops which we observe. For precipitates with number density $3 \times 10^{15} \text{ cm}^{-3}$ and average size $120 \text{ \AA}$, the time required for dissolution in the solid state (at 1100°C) was calculated to be at least 1 min. The time required for removal of dislocation loops under similar conditions was calculated to be about 6 min. These dissolution times are unrealistically long compared to the laser pulse duration time. It should be pointed out

that these estimates of times would be lowered by less than a factor of 2 if ionization enhanced diffusion due to laser radiation were included, because migration energies of interstitials constitute only a small part of the activation energy for diffusion in silicon.

The increase in the defect free depth with increasing laser energy density is a consequence of the increased melt front penetration at higher pulse energy densities. The increase in the depth of annealing with additional pulses and the saturation after ~ 5 pulses can be understood if there are changes in the absorption coefficient in the annealed region compared to the unannealed region containing loops and precipitates. Although the observed behavior can be accounted for qualitatively by either an increase or decrease of the absorption coefficient of the annealed zone relative to the substrate; in the present case it seems likely that an increase in the absorption coefficient in the annealed region occurs due to the increased phosphorus in solution giving rise to increased free carrier absorption.³ During the second and latter pulses more energy is absorbed in the annealed zone, leading to higher temperatures and presumably greater melt thickness. Saturation in the depth of annealing occurs when essentially all of the available energy of the laser pulse is absorbed in the annealed region with the depth of melting then being determined by the total energy available. The effects of pulse duration time and energy density on the thickness of the melt zone can also be explained by recent calculations⁴ of the penetration depth of the melted region.

The study of laser annealing in ion implanted silicon as a function of pulse energy density (50 n sec) indicated that there is a threshold in the energy density above which a complete annealing of the damage and a full recovery of electrical properties are realized. Below this threshold incomplete annealing occurs which is accompanied by partial electrical recovery. For the case of As⁺ implanted (a dose of $1.4 \times 10^{16} \text{ cm}^{-2}$ produced an amorphous layer 1600 Å thick) silicon, a 0.63 J cm^{-2} pulse led to a polycrystalline $1000 \pm 200 \text{ Å}$ thick, with a 400 - 600 Å amorphous layer between it and the single crystal substrate. Fig. 2 shows clearly the termination

Fig. 2. Bright-field electron micrograph of a arsenic implanted specimen showing the existence of both polycrystalline and amorphous layers with a pulse of 0.63 J cm^{-2} , $\tau = 50 \text{ n sec}$.

of the polycrystalline layer and the amorphous layer at the termination of the amorphous region on the single crystal substrate is indicated at A. When the energy density of the pulse was increased to 0.82 J cm^{-2} , the amorphous layer was eliminated and a polycrystalline layer of larger average grain size was observed. Further increase in the energy density to 1.07 J cm^{-2} led to complete return of the implanted layer to the substrate crystal orientation but with residual damage in the form of dislocation tangles present in a region about $200\text{\AA}$ thick near the surface. With higher pulse energy densities (1.1 J cm^{-2}), a complete annealing was observed. The above sequence of annealing structures was also observed in a specimen irradiated with a single laser pulse of non-uniform energy density. These microstructures correlate

Fig. 3. Bright-field electron micrograph of a boron implanted, laser annealed ($E = 1.1 \text{ J cm}^{-2}$, $\tau = 50 \text{ n sec}$) specimen showing annealed, defect-free regions and the regions containing dislocation tangles and loops near the surface region $\sim 200\text{\AA}$ thick.

well with electrical measurements which indicated only partial recovery of electrical properties below 1.1 J cm^{-2} with complete recovery above this value. The above observations suggest that with a laser pulse of 0.63 J cm^{-2} , a layer of about $1000\text{\AA}$ is melted for a time interval long enough for crystallization to occur. At 0.82 J cm^{-2} the above melted region presumably stops just short of the boundary between the amorphous layer and the substrate. With the 1.07 J cm^{-2} laser pulse, the whole amorphous layer remains molten long enough for crystallization from the substrate to occur however the temperature near the surface probably drops below the melting point just before the crystallizing interface reaches the free surface. The surface layer ($\sim 200\text{\AA}$ thick) still grows in correlation with the crystallizing interface, probably by a solid phase epitaxial process. For pulse energies $> 1.1 \text{ J cm}^{-2}$, the implanted layer remains molten for sufficiently long time that the crystallization of whole amorphous layer is completed by the liquid phase epitaxial process.

Fig. 4. Bright-field electron micrograph of a phosphorus implanted, laser annealed ($E = 1.1 \text{ J cm}^{-2}$, $t = 50 \text{ ns}$) showing a periodic structure of annealed and unannealed (dislocation loops and tangles near the surface) regions.

Boron implanted (35 keV , $1.0 \times 10^{15} \text{ cm}^{-2}$) silicon crystals are heavily damaged but not made completely amorphous by the implantation. Specimens irradiated with a laser pulse of 1.1 J cm^{-2} contained mostly completely annealed, defect-free regions with a few places where the damage in the form of dislocation tangles and loops was observed in the first $200\text{\AA}$ layer from the free surface. This is attributed to inhomogeneity in energy density across the laser beam. Fig. 3 shows both the defect-free regions and the regions containing loops and dislocations near the surface.

The results from phosphorous implanted specimens (dose = $1.0 \times 10^{15} \text{ cm}^{-2}$) irradiated by a laser pulse of 1.1 J cm^{-2} are shown in Fig. 4. This energy density is very close to the threshold value for a complete annealing. In this figure, a circular defect-free region is surrounded by regions containing dislocations and tangles localized within $\sim 200\text{\AA}$ of the surface alternating with defect free regions with a periodicity of $\sim 0.75 \mu\text{m}$. Since there is no simple correlation of this period with the ruby laser wavelength, it can not be interpreted as resulting from interference across the laser beam.⁵ We are currently investigating whether this periodicity is related to a non-linear interaction between simultaneously oscillating axial modes of the laser.⁶

In summary, the pulsed laser irradiation used in this investigation leads to melting by which dislocation loops and precipitates in thermally diffused silicon can be removed up to depths of about one micron. For a complete annealing of displacement damage in ion implanted silicon, a minimum pulse energy density for the melting of whole implanted layer is required so that single crystal substrate can provide a seed for a liquid phase epitaxial growth.

*Research sponsored by the Division of Materials Sciences, U.S. Department of Energy under contract W-7405-eng-26 with the Union Carbide Corporation.

REFERENCES

1. J. Narayan, R. T. Young and C. W. White, J. Appl. Phys. 49, 3912 (1978) and references there in.
2. P. Baeri, S. U. Campisano, G. Foti and E. Rimini, Phys. Rev. Lett. 41, 1245 (1978); C. W. White, J. Narayan, B. R. Appleton and S. R. Wilson, J. Appl. Phys. (in press).
3. J. M. Poate, (unpublished).
4. J. C. Wang, R. F. Wood and P. P. Pronko, Appl. Phys. Lett. 33, 455 (1978); P. Baeri, S. U. Campisano, G. Foti and E. Rimini, J. Appl. Phys. (in press).
5. H. J. Leamy, G. A. Rozgonyi and T. T. Sheng, Appl. Phys. Lett. 32, 535 (1978).
6. G. Marcas, G. L. Harris, C. A. Lee and R. A. McFarlane, Appl. Phys. Lett. 33, 453 (1978).