Lawrence Berkeley Laboratory
UNIVERSITY OF CALIFORNIA

Materials & Chemical Sciences Division

National Center for Electron Microscopy

Presented at the Electron Microscopy Society of America
Conference, San Jose, CA, August 4-8, 1991,
and to be published in the Proceedings

Received 11/22/91

DEC 17 1991

HREM Imaging of Single Unit Cell Carbide Precipitates in Pt-C Alloys

M.J. Witcomb, U. Dahmen, M.A. O'Keefe, and K.H. Westmacott

July 1991

DISCLAIMER

This document was prepared as an account of work sponsored by the United States Government. Neither the United States Government nor any agency thereof, nor The Regents of the University of California, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by its trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or The Regents of the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof or The Regents of the University of California and shall not be used for advertising or product endorsement purposes.

Lawrence Berkeley Laboratory is an equal opportunity employer.

LBL--30693

DE92 004320

HREM Imaging of Single Unit Cel Carbide Precipitates in Pt-C Alloys

M.J. Witcomb*, U. Dahmen, M.A. O'Keefe and K.H. Westmacott

**Electron Microscope Unit
University of the Witwatersrand
Johannesburg, South Africa*

*National Center for Electron Microscopy
Materials Sciences Division
Lawrence Berkeley Laboratory
University of California, Berkeley, CA 94720*

Proc. EMSA/MAS Meeting, San Jose, 8/4-8/9/91

This work was supported in part by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Science Division of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098.

MASTER

2

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

HREM IMAGING OF SINGLE UNIT CELL CARBIDE PRECIPITATES IN Pt-C ALLOYS

M.J. Witcomb*, U. Dahmen, M.A. O'Keefe and K.H. Westmacott

National Center for Electron Microscopy, Lawrence Berkeley Laboratory, Berkeley

*Electron Microscope Unit, University of the Witwatersrand, Johannesburg

Dilute Pt-C alloys are prototypical for studying oversize carbide phase precipitation from interstitial solid solution. Earlier studies showed the essential function of quenched-in vacancies in the precipitation process¹. Vacancies play a dual, volume accommodation and structural, role in the transformation by modifying both the habit plane spacing and stacking sequence². It was also shown how the precipitation sequence in interstitial Pt-C alloys is analogous to that in substitutional Al-Cu alloys. Initially a "GP zone" consisting of a monolayer plate of carbon atoms and vacancies forms. Atomic resolution images of the so-called α precipitates have confirmed their structure³. During subsequent coarsening of the precipitates, α' platelets form. Schematic diagrams illustrating the α and α' structures in $\langle 100 \rangle$ projection are given in Fig. 1. The single-layer α structure, or GP zone is identical to a $\{100\}$ stacking fault stabilized by an intercalation of carbon. The two-layer α' structure is the first true precipitate phase and has a crystal structure anti-isomorphous with calcium fluoride. In the present contribution, simulated images based on this structure are compared with experimental images obtained at 800kV on the JEOL-1000 ARM. In addition to confirming the proposed precipitate structure, the results show the potential for successful imaging of precipitate structures containing light elements.

Due to a strong $\langle 112 \rangle$ foil texture, it was difficult to obtain high resolution images in low-index orientations. The high angle tilt goniometer of the ARM allowed imaging in both the $\langle 110 \rangle$ zone axis at about 30° from the foil normal and the $\langle 100 \rangle$ zone axis at about 35° from the foil normal. Although only a single unit cell thick, the plates are of substantial diameter. Through-focus series of images were recorded near the thin edge of the foil. Earlier results obtained at the $\langle 110 \rangle$ zone axis were in agreement with the model structure but image simulations showed that the sensitivity to the presence of carbon atoms was far greater in a $\langle 100 \rangle$ zone. Fig. 2 shows images of α' plates in $\langle 100 \rangle$ orientation, recorded at -40 (a) and -80nm (b) defocus. Atomic columns in the matrix are black in (a) and white in (b).

The corresponding image simulations are shown in Fig. 3. The projected potential is illustrated in (a) and the two defocus conditions equivalent to those in the experimental images in Fig. 2 are seen in (b) and (c). Note that the carbon atoms are not directly resolved under either defocus condition but give rise to a bridged intensity between Pt atom dots. However, the effect of the presence of carbon is clearly apparent by comparison with images simulated for the same imaging conditions and the same Pt atom configuration but without the carbon atoms. This is shown in Fig. 3 (d-e). These results directly confirm the structure model proposed earlier and provide a more sensitive probe for the presence of carbon than similar images in $\langle 110 \rangle$ orientation⁴.

References

1. K.H. Westmacott, M.J. Witcomb and U. Dahmen, *Acta Met.* **31**, 743, 755 (1983)
2. K.H. Westmacott and U. Dahmen, 2nd Acta/Scripta Metallurgica Conference, Pergamon Press, P. Haaser, V. Gerold, R. Wagner and M.F. Ashby (eds.), p. 204 (1984)
3. M.J. Witcomb, U. Dahmen and K.H. Westmacott, *EMSSA Proc.* **20**, 43 (1990)
4. This work is supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Materials Sciences Division of the U.S. Department of Energy under Contract No. DE-ACO3-76SF00098.

Fig. 1.--Schematic illustrations of the single layer α and double layer α' platinum carbide precipitate structures in $\langle 100 \rangle$ projection with carbon atoms shown as small black circles and the alternate ABAB stacking of Pt atoms in $\{100\}$ layers indicated by shading.

Fig. 2.--High resolution images of $\{001\}$ α' plates seen on edge in $\langle 100 \rangle$ zone axis orientation. The foil was tilted by about 35° . The image in (a) was obtained in the JEOL ARM 1000 at 800kV and a defocus of -40nm and that in (b) at -80nm .

Fig. 3.--Image simulations for the conditions of fig. 2 at a foil thickness of 4nm , 800kV and 0.03nm vibration, with projected potential (a), -40nm defocus (b) and -80nm defocus (c). The same configuration but without the carbon atoms is shown in (d)-(f). Note clear effect of carbon. Only the carbon-containing model matches the experimental images in fig. 2

END

**DATE
FILMED**

01 / 23 / 92