LEACH TESTING OF IN SITU STABILIZATION
GROUTS CONTAINING ADDITIVES TO
SEQUESTER CONTAMINANTS .

R. J. Serne	V. L. LeGore
L. L. Ames	C. W. Lindenmeier
P. F. C. Martin	S. J. Phillips ^(a)

April 1993

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

(a) Westinghouse Hanford Company
Richland, Washington 99352

MASTER

SUMMARY

This document discusses laboratory testing performed by Pacific Northwest Laboratory (PNL) for Westinghouse Hanford Company (WHC) of special grout formulations that incorporate specific sequestering agents to help improve the ability of the cement to resist contaminant leaching.

A fluidized-bed cement injection system is being designed and will be demonstrated by WHC for the in situ isolation and stabilization of radioactive and hazardous chemical wastes disposed of in and near underground waste disposal and containment structures. The fluidized-bed system will mechanically homogenize and incorporate waste tank residuals (tank bottoms and sludges) with selected additive materials to provide chemical fixation. Successful demonstration of this technology will permit unrestricted access to waste disposal sites that are presently considered unsafe because of their potential for collapse.

To enhance the sequestering of contaminants we chose five additives to introduce (singly) to the control cement. The additives were Florida pebble phosphate, clinoptilolite (a natural zeolite), ferrous sulfide (a reductant), a mixed bed organic ion exchange resin and a proprietary anion-adsorbing mixed metal oxide. These additives were added one per test to the standard formulation and used to encapsulate a diluted high-salt alkaline liquid waste that is produced after various processes to remove uranium and plutonium from spent nuclear fuel.

Grouts cured for 28 days were leach tested following ANSI6.1 protocols for 84 days. Contaminants that were monitored include TcO_4^- , CrO_4^{2-} , Cs^+ , SeO_4^{2-} , Sr^{2+} , and NO_3^- .

No additive greatly enhances the leach resistance of the standard formulation for all five contaminants. However, for specific contaminants a specific additive may show improvement over the grout itself. Cesium retention is improved by many of the additives. None of the additives appears to improve significantly the leach resistance of NO_3^- , CrO_4^{2-} , or SeO_4^{2-} . Clinoptilolite and pebble phosphate appear to have significant detrimental effects on anion leaching compared to the standard formulation.

Pertechnetate (TcO_4^-) anion leaches fairly rapidly from the control formulation. The additives clinoptilolite and pebble phosphate have a detrimental effect on Tc sequestering. The additives FeS and mixed bed exchange resin improve the leach resistance of the grouts for TcO_4^- very dramatically. FeS likely reduces TcO_4^- to lower valence states Tc (III, IV) that form insoluble oxides in the waste form pores. The mixed bed ion exchange resin likely adsorbs the TcO_4^- anion and retards its release from the grout.

All the grout waste forms retain Sr^{2+} quite strongly. The grout with the anion adsorbing metal oxide additive leaches the least Sr, but this improved retention of Sr is unexplained.

The present study has identified ^{137}Cs and ^{99}Tc as two contaminants for which an additive could greatly increase the leach resistance of the standard injectable formulation. The user should characterize the wastes present in the field disposal unit, rank the contaminants' long-term hazard potential, and choose additives to improve the leach resistance of the contaminants that exhibit larger potential hazards. Before finalizing the additive choice, the operator should always consider whether the additive would deleteriously affect the leach resistance of other high-risk contaminants also present in the disposal unit. Systems performance assessments using leach data, site specific soil, hydrologic, and release scenarios can be performed to develop objective cost-benefit analyses of various grout injection remediation schemes.

CONTENTS

SUMMARY	iii
INTRODUCTION	1
CHOICE OF ADDITIVES	3
ALCOA MIXED METAL OXIDE	3
FLORIDA PEBBLE PHOSPHATE ROCK	4
FERROUS SULFIDE	5
CLINOPTILOLITE	7
MIXED BED ION EXCHANGE RESIN	8
FABRICATION OF GROUT SPECIMENS	9
DESCRIPTION AND RESULTS OF LEACH TESTS	15
DISCUSSION OF LEACH RESULTS	19
REFERENCES	23
APPENDIX - DETAILS ON SPECIMEN SIZE AND ANS 16.1 LEACH TESTS	A.1

TABLES

1	Average of 30 Florida Pebble Phosphate Rock Chemical Analyses and Structural Formula	5
2	Calculated Double-Shell Slurry Feed Concentrations	10
3	Volume Percent Formulations for In Situ Grout	11
4	Weight Percent Formulations for In Situ Grout	11
5	Bulk Densities of Grout Materials	11
6	Average Compressive Strength of Grout/Additive Samples	12
7	Activities in nCi/g or $\mu\text{g/g}$ Within Test Specimens	13
8	Leach Results After 84 Days of Leaching	16
9	Average Leachate pH Values Over Seven Sampling Times	17
10	Average Leachate pH Values for All Grouts	17

INTRODUCTION

U.S. Department of Energy (DOE) sites across the nation have used hundreds of cribs, caissons, and other buried liquid waste disposal and containment structures over the years. Many of these inactive liquid waste disposal structures still contain significant quantities of radioactive and other hazardous chemical wastes in sludges and entrained pore water that pose immediate radiological and industrial safety hazards because of their physical instability. Risk management is currently being accomplished through administrative controls, or in some cases, prohibited access to sites.

The technology proposed in this report will allow restrictions on site access to be eliminated by providing physical stability and chemical isolation of the waste disposal sites. Furthermore, the characterization of unstable waste disposal sites will be required during Comprehensive Environmental Response, Compensation, and Liability Act (CERCLA) site remedial investigations. Physical stability will be required to support these site drilling operations.

A fluidized-bed grout injection system is being designed and will be demonstrated by Westinghouse Hanford Company (WHC) for the in situ isolation and stabilization of radioactive and hazardous chemical wastes disposed of in and near, underground waste disposal and containment structures. The fluidized-bed system will mechanically homogenize and incorporate waste tank residuals (tank bottoms and sludges) with selected additive materials to provide chemical fixation. Particulate- and solution-based grout materials will then be incorporated into the interstitial void volume of the disposal structures and surrounding geologic media to provide enhanced chemical isolation and physical stabilization. Successful demonstration of this technology will permit unrestricted access to waste disposal sites that are currently considered unsafe because of their potential for collapse. Additional details on the mobile field equipment can be found in Phillips et al. (1992).

The potential for migration of contaminants and associated health risks will be greatly reduced by providing a waste form that is physically and chemically stable and isolated from potential driving forces (e.g.,

percolating water) that can result in contaminant migration. Successful in-place disposal of wastes will also reduce risk to workers when compared with the retrieval, packaging, and redisposal options.

This document discusses laboratory testing performed by Pacific Northwest Laboratory for WHC of special cement formulations that incorporate specific sequestering agents to help improve the ability of the solidified grout to resist contaminant leaching. Past work with neat (pure) portland cements have shown that some contaminants are not readily sequestered within the solidified waste form (e.g., ^{137}Cs , ^{129}I , NO_3^- , TcO_4^- , [Serne and Wood 1990; Matsuzuru and Ito 1977]). We performed standard leach tests on the baseline injectable grout (three parts class F fly ash, two parts water and one part portland type I/II cement) and grout with specific solid sequestering agents (e.g., zeolite and ion exchange resin). The results of these tests are described here.

The in situ grout injection technology could be implemented as a precursor to protective barrier construction to provide a physically stable substrate on which to construct barriers and mitigate potential impacts on barrier performance as a result of waste site subsidence.

CHOICE OF ADDITIVES

The criteria used to choose the additives for the grout/waste solidification/encapsulation required that the additive(s)

1. must be operative and stable in a pH range of 10 to 13 typically found in cement pore waters
2. must have a high exchange capacity or ion selectivity. Further, additives that are selective for anions or anion complexes and additives that oxidize to produce reducing conditions for radionuclides with more than one oxidation state are especially needed.

The following paragraphs describe the five additives and the reasons for their choice. The additives were Florida pebble phosphate, clinoptilolite (a natural zeolite), ferrous sulfide (a reductant), a mixed-bed organic ion exchange resin (mixed bed IEX) and a proprietary anion-adsorbing mixed metal oxide (Alcoa Sorbplus mixed metal oxide).^(a) All additives are commercially available; some are more expensive than others. Least expensive are Florida pebble phosphate and clinoptilolite, followed by FeS, organic resin (Amberlite MB-1),^(a) and most expensive, mixed metal oxide.

ALCOA MIXED METAL OXIDE

Mixed metal oxide is a mixed metal oxide/hydroxide proprietary product manufactured by the Aluminum Company of America (Alcoa) for use as a high-capacity anion adsorbent. It is powder to granular in form, with a 1% slurry in water yielding a pH of 11 to 12. With this pH, the material is best kept in sealed containers, or under a CO₂-free atmosphere before use. Otherwise, the product will absorb CO₂ from the air over a period of time and become a metal carbonate rather than a metal hydroxide, considerably diminishing its anion exchange properties. This will reduce the anion selectivity as well because, according to Alcoa Separations Technology Division Application Data Sep 922, the replacement series is CO₃²⁻ > As(III) > SO₄²⁻ > Cr(VI) > As(V) > Se(VI) ≈ Se(IV) > Cu•citrate > Cu•EDTA > Ni•EDTA at pH 10. Hence, mixed metal

(a) The identification of the commercial products is made only to clarify technical details. PNL does not determine suitability or compare the efficiency of commercial products.

oxide is selective for CO_3^{2-} and should be kept away from CO_2 before use. It should not be used in environments containing appreciable carbonate. It is typically used in the cleanup of metal finishing wastes and other wastes containing Cr(VI), complexed metals, selenium, or arsenic.

After sitting in air for 24 h, the mixed oxide gained 2% by weight, presumably as a result of CO_2 or water absorption. Drying the product at 80°C for 24 h, results in a 6% by weight loss of water. These attributes (CO_2 absorption and partially wet state) should be considered in field testing.

The goal in adding the mixed metal oxide to the grout/waste was to remove and retain radionuclides present in the waste in the form of soluble anions or anionic complexes (e.g., AsO_4^{2-} , SeO_4^{2-} , CrO_4^{2-} , TcO_4^-). This is not easily done at the higher alkaline pH values typical of a grout environment (pH 10 to 12), which is why the commercial product was tested for this application.

FLORIDA PEBBLE PHOSPHATE ROCK

Florida pebble phosphate rock is a complex carbonate fluorapatite. A typical chemical analysis and formula is given in Table 1. The principal constituent that characterizes marine apatites such as the Florida pebble phosphate rock is the carbonate that substitutes for phosphate; hence the descriptive compositional name of carbonate fluorapatite for the Florida pebble phosphate rock. It is a commercial source of phosphate rock for manufacture of fertilizers and phosphorus. The pebble phosphate is a bundle of many small carbonate fluorapatite crystals radiating from the center of a spherical aggregate from 1 mm to 1 cm in diameter (Reisenauer and Ames 1961). Diffusion of ions along radial crystal boundaries results in removal of sorbing ions from availability for immediate exchange reactions on rock surfaces.

The pebble phosphate rock used does not gain or lose any weight upon contacting air or being heated to 80°C for 24 h. The material would likely be physically stable for long periods in bins used in the portable mixing module.

TABLE 1. Average of 30 Florida Pebble Phosphate Rock Chemical Analyses and Structural Formula (after McClelland and Lehr 1969)

	wt%	Formula
CaO	43.70	
MgO	0.32	$(\text{Ca}_{9.7}, \text{Mg}_{0.1}, \text{Na}_{0.2})[(\text{PO}_4)_{5.1}(\text{CO}_3)_{0.7}(\text{CO}_3, \text{F})_{0.2}]\text{F}_{2.0}$
Na ₂ O	0.51	
P ₂ O ₅	29.90	Total Cation Charges = +19.8
CO ₂	3.10	Total Anion Charges = -19.3
F	3.50	

The goal for adding pebble phosphate rock was to exchange heavy metal ions such as uranium and plutonium from solution and to furnish a sink for the sorbed ions as they diffuse down crystalline interface boundaries within the apatite pebbles.

FERROUS SULFIDE

Pyrrhotite, or FeS, was chosen as the sulfide to be tested as a grout additive because pyrite, FeS₂, oxidation reaction produces excess acid that could have detrimental effects on the physical and chemical integrity of the grout monolith. The FeS used in these studies appears to be stable in contact with air or after heating to 80°C for 24 h.

Chemical weathering involves reaction at the interface between solid grains and a mobile medium. The diffusion of charged particles in solids is almost negligible compared to their movement in solution. The important exception is the movement of electrons. They can be viewed as chemical species that can move through solids that are electronic conductors. Such solids include most sulfides and it is this conductive property that dominates their reactivities. For a nonconductive mineral such as calcium carbonate (calcite) to be attacked by acid, for example, the whole reaction occurs at the calcite surface/solution interface. An acid H⁺ has to move to the calcite surface and the solubilized Ca²⁺ and HCO₃⁻, then move away, a complicated, to-and-from interaction relying on diffusion in the aqueous medium. In contrast, in conducting minerals, the process of oxidation and reduction can be separated by

some distance and still function by the mechanism of an electrochemical cell. The anode involves the general reaction with one-to-one, metal-to-sulfur compounds: $MS + 4 H_2O \rightarrow M^{2+} + SO_4^{2-} + 8 H^+ + 8 e^-$. The net amount of base produced from the cathodic reduction of oxygen is, $O_2 + 2 H_2O + 4 e^- \rightarrow 4 OH^-$. Combining the two reactions to complete the cell one obtains, $MS + 2 O_2 \rightarrow M^{2+} + SO_4^{2-}$ (Thorner 1983). The symbol MS represents a mineral such as pyrrhotite, FeS, a common ore mineral and also available in technical grades as an ore smelting byproduct. Pyrite also is a common, naturally occurring sulfide mineral, FeS_2 , composed of a cubic cell arrangement of Fe^{2+} and S_2^{2-} ions. However, pyrite, with a higher sulfur-to-metal ratio than pyrrhotite, reacts during oxidation as follows:

to produce two moles of acid for each mole of pyrite oxidized.

The oxidation of the ferrous iron in the above equation can potentially produce even larger quantities of acid by hydrolysis

when the sulfide reaction environment is buffered at a pH below 7.0. This acid production would not be encountered in an alkaline system above pH 7, such as that present in cement pore water. Only a minor amount of Fe(II) would be in solution as Fe^{2+} and $Fe(OH)^+$. Most iron will have precipitated as the so-called "green rust" forms, or be tied up as insoluble $Fe(OH)_2$. Oxidation of the $Fe(OH)_2$ in a high pH environment results in the reaction

producing no acid and forming a precipitate that retains heavy metals by specific adsorption. The cathodic reduction of oxygen provides the driving force for the whole redox process. If there is no contact with air, dissolved in solution or otherwise present, there will be no redox process.

Radionuclide mobilities are affected by a variety of environmental factors such as pH, redox potential, pH buffering, and water movement. The goal of the ferrous sulfide oxidation is to favorably manipulate the redox potential because radionuclides in lower oxidation states are often less soluble. Uranium is a good example. Uranium as U(VI) is very soluble both as

complexes such as $[\text{UO}_2(\text{CO}_3)_2]^{2-}$ and as the uranyl ion in acidic solutions. On the other hand, reduction of U(VI) to U(IV) results in much less solubility (Early et al. 1982). Many of the radionuclides with variable oxidation states (Se, Sb, U, Pu, Np) can be reduced if they are in the vicinity of the FeS oxidation reaction. This reduction is one of the goals of FeS addition to the grout/waste mixture. The other goal rests on the FeS oxidation end product, hydrated iron oxides. Adsorption of cation species is expected on the iron oxides, plus some sorption of anion species (Thornber 1983), which tend to sorb less at higher pH values.

CLINOPTILOLITE

Clinoptilolite is a member of the zeolite family of minerals. Zeolites are very common in the arid western United States, occurring as micro-crystalline masses of sedimentary origin as a result of alteration of volcanic eruptive rocks by saline groundwaters and alkaline lake waters (Hay 1963, 1978). Hay's work is especially valuable because his clinoptilolite came specifically from the same area of origin as the clinoptilolite used in this study.

A zeolite mineral is a three-dimensional framework aluminosilicate whose structure contains channels of specific and fixed dimensions filled with water and exchangeable cations. The basic building block of the zeolite framework is the silicon tetrahedron, $(\text{SiO}_4)^0$, with all oxygens shared by two silicons. If only silicon made up the framework tetrahedrons, the chemical formula would be Si_nO_{2n} , but with Al in the tetrahedra, the formula becomes $[\text{Al}_m\text{Si}_{n-m}\text{O}_{2n}]^{m-}$ with the m negative charges balanced by the usually exchangeable, extra framework cations K, Na and Ca, or less frequently Li, Mg, Sr, and Ba. With univalent and divalent extra framework cations, the general formula for a zeolite mineral becomes:

Specifically, the formula for the sedimentary clinoptilolite used in this study is Si/Al of 4.0 to 5.1, K and Na exchangeable cations predominating and water molecules per Al atom of 3.0 to 3.5 (Hay 1978). The cation exchange properties of clinoptilolite are reasonably well known (Ames 1960) including several applications to radioactive waste cleanup (Mumpton 1977). The acquisition cost of natural clinoptilolite for applications at DOE's Hanford Site is relatively low because it is surface-mined or quarried not more than 650 km from the Hanford Site. For these reasons, past experiences with clinoptilolite, and the cost factor, clinoptilolite was chosen as a cement additive. The goal is to increase the type and amounts of radionuclides retained in the grout/waste solid by adding clinoptilolite to the system. Clinoptilolite addition is considered the base case against which all other additives will be compared. The clinoptilolite under study appears stable in air but did lose 4% weight during drying at 80°C for 24 h. When fully hydrated clinoptilolite contains 12 to 15 wt% zeolitic water. Some of this water can be removed upon extreme drying conditions in the field.

MIXED-BED ION EXCHANGE RESIN

This ion exchange resin (mixed-bed resin) is actually two resins, both styrene-divinyl benzene crosslinked, to produce strong acid and strong base exchangers. In the strong acid resin case, sulfonation with sulfuric acid of the styrene-DVB copolymer results in a cation exchanger, while introduction of trimethylamine into a chloromethylated styrene-DVB copolymer results in a strongly basic anion exchanger. Hence, the resin is half in the hydrogen form and half in the hydroxyl form. The cation/anion exchange capacity of the resin is relatively high at 4.1 meq/mL and it can operate at 140°F. The resin is primarily used in water deionization and should remove and retain both cationic and anionic radionuclide forms. The goal is to remove both radionuclide forms from the waste solution and retain them in the grout/waste. This resin also was chosen for use because it is less costly than many of the newer resins that would remove both anionic and cationic forms from the waste.

Resins are generally fully saturated with water when received and will lose water upon contact with dry air (8% weight loss in 24 h in lab) or heating (22% weight loss upon heating to 80°C for 24 h). Although the materials will rewet upon mixing with grout, the actual mixing of resin with other dry grout constituents may be more difficult to homogenize.

FABRICATION OF GROUT SPECIMENS

The standard formulation that will be injected into inactive disposal unit voids is mixed in the field using a standard mix ratio of three parts fly ash, two parts water, and one part Portland cement by volume. In this laboratory study to determine the efficacy of using selected sequestering agents to improve contaminant retention, the water was replaced by diluted (1 part liquid waste to 2 parts tap water) simulated double-shell slurry feed (DSSF) liquid waste spiked with radionuclides. DSSF is currently stored in double-walled tanks on the Hanford Site. The liquid is a concentrated salt solution created upon neutralization of acidic liquid wastes that occur from the recovery of uranium and plutonium from irradiated fuel elements. Table 2 lists the composition of DSSF before dilution with tap water.

Before mixing the fly ash, cement, sequestering agents, and diluted liquid waste the sequestering agents ferrous sulfide, Florida pebble phosphate and clinoptilolite were ground to pass through 40 mesh ($<325 \mu\text{m}$). The mixed metal oxide and mixed bed IEX resin were already disaggregated as received. Variable amounts of simulated waste solution, cement, and fly ash were mixed with an arbitrarily fixed volume of sequestering agent in an attempt to keep the processability (viscosity) of the slurries approximately equal. The amount of admixtures (sequestering agents) was held constant at 22 vol%. We also attempted to keep the formulations close to the commonly used field formulation.

Table 3 shows the formulations used on a volume percentage basis while Table 4 shows the formulations on a weight basis. Two values are presented for the mixed metal oxide formulation because a minor error in mixing occurred for the samples spiked with gamma emitting tracers. The mixing error likely has insignificant effects on the leaching data. The bulk density of each solidification agent is given in Table 5.

The first samples prepared contained no radionuclides and after curing at room temperature (in sealed containers to minimize moisture loss) were used to measure compressive strength. The grout formulations presented in Tables 3 and 4 produce a slurry that yields a viscosity of $166 \text{ mPa}\cdot\text{s}$ ($24 \text{ lb}\cdot\text{s}/\text{in}^2$).

TABLE 2. Calculated Double-Shell Slurry Feed Concentrations (mg/L)

<u>Constituent</u>	<u>Concentration</u>
Ag	324
Al	40,470
As	0.06
Ba	1,247
Cl	7,729
Ca	400
Cd	15.7
Cu	12.7
Fe	2,815
Hg	5.9
K	19,432
Mn	5,494
Mo	96.9
Na	241,390
B	210
Cr	2,309
Ni	59
Pb	5
Se	8.7
Zn	3,250
SO ₄	10,080
OH	69,700
F	1,120
CO ₃	17,940
NO ₃	308,760
NO ₂	45,950

TABLE 3. Volume Percent Formulations for In Situ Grout

	<u>Control</u>	<u>FeS</u>	<u>Pebble Phosphate</u>	<u>Clinop- tilolite</u>	<u>Mixed Bed Ion Exchange</u>	<u>Mixed Metal Oxide</u>
Fly Ash	48.00	32.00	33.33	30.77	34.20	29.08 (30.08) ^(a)
Cement	16.00	10.67	11.11	10.26	11.40	9.69 (10.03)
Admixture	0.00	22.22	22.22	22.22	22.22	22.22 (22.98)
Waste	36.00	35.11	33.33	36.75	32.18	39.00 (36.92)

(a) = Values in parentheses are for grouts with γ -emitters

TABLE 4. Weight Percent Formulations for In Situ Grout

	<u>Control</u>	<u>FeS</u>	<u>Pebble Phosphate</u>	<u>Clinop- tilolite</u>	<u>Mixed Bed Ion Exchange</u>	<u>Mixed Metal Oxide</u>
Fly Ash	51.42	25.99	34.22	37.57	41.26	36.29 (37.53) ^(a)
Cement	17.89	9.04	11.91	13.07	14.36	12.63 (13.06)
Admixture	0.00	42.28	26.64	13.66	13.50	12.35 (12.77)
Waste	30.69	22.69	27.23	35.70	30.88	38.73 (36.65)
Mix Ratio ^(b)	20.52	30.95	24.28	16.36	20.33	14.37 (15.70)

(a) = Values in parentheses are for grouts with γ -emitters.

(b) = Mix ratio is amount of solids binding agent used per volume of liquid waste units lb/gal. To convert to metric units, g/l, multiply by 119.8.

TABLE 5. Bulk Densities of Grout Materials (g/cm³)

Cement	1.43	Fly Ash	1.37
Ferrous Sulfide	3.21	Pebble Phosphate	1.60
Clinoptilolite	0.69	Mixed Bed Ion Exchange	0.69
Mixed Metal Oxide	0.61	DSSF Liquid Waste	1.27

The grout made with the mixed-bed exchange resin was less viscous at 61 MPa•s (8.8 lb•s/in²). The compressive strength of these grout specimens was measured after 36 days (39 days for the mixed metal oxide) of curing. Results are shown in Table 6. American Society for Testing Materials Method C39-84 (ASTM 1985) was used to measure compressive strength.

The compressive strength of grouts containing synthetic additives (mixed bed and mixed metal oxide products) is lower than grouts containing natural geologic media additives. The addition of additives at the expense of cement and fly ash lowers compressive strengths in comparison to the control. The observed compressive strengths are still adequate to instill stability under most shallow-land disposal scenarios.

Grout mixtures traced with radionuclides were prepared March 29, 1991 using a small volume mixer. One set of grouts was made with γ -emitting radionuclides added to the diluted DSSF liquid waste. Radionuclides included ¹³⁷Cs as CsCl (~100 μ Ci/L), ⁸⁵Sr as SrCl₂ (~200 μ Ci/L), ⁵¹Cr as Na₂CrO₄ (~500 μ Ci/L), and ⁷⁵Se as Na₂SeO₄ (~100 μ Ci/L). The second set of grouts contained ⁹⁹Tc as NH₄TcO₄ (~100 μ Ci/L). Small batches of grouts with the formulations shown in Tables 3 and 4 were prepared. Grout slurry was poured into cylindrical molds with the dimensions 3.18-cm diameter by 3.6- to 4.2-cm length. The molds were sealed to minimize evaporation and samples cured at room temperature. After 28 days of curing the leach tests were begun (April 26, 1991). The activities of radionuclides in the cured grouts are shown in Table 7.

TABLE 6. Average Compressive Strength of Grout/Additive Samples

<u>Admixture type</u>	<u>psi</u>	<u>MPa</u>
Control	1777	12.25
Pebble Phosphate	1552	10.70
Ferrous Sulfide	1342	9.25
Clinoptilolite	1269	8.75
Mixed Bed Ion Exchange	843	5.81
Mixed Metal Oxide	646	4.46

TABLE 7. Activities in nCi/g or mg/g Within Test Specimens

	<u>Control</u>	<u>Fes</u>	<u>Pebble Phosphate</u>	<u>Clinop- tilolite</u>	<u>Mixed Bed Ion Exchange</u>	<u>Mixed Metal Oxide</u>
⁵¹ Cr	35.5	26.3	31.5	41.3	35.7	42.4
⁷⁵ Se	20.0	14.8	17.7	23.2	20.1	23.9
⁸⁵ Sr	42.7	34.9	41.9	55.0	47.5	56.4
¹³⁷ Cs	22.8	16.8	20.2	26.5	22.9	27.2
⁹⁹ Tc	24.6	18.2	21.9	28.7	24.8	31.1
Nitrate ^(a)	20.5	15.2	18.2	23.9	20.6	25.9 ^(b) 24.5 ^(c)

(a) mg/g.

(b) For Tc-bearing samples.

(c) For γ-bearing samples.

DESCRIPTION AND RESULTS OF LEACH TESTS

After the 28-day cure the radioactive specimens were removed from their molds and suspended in tap water using nylon monofilament. Following ANS 16.1 protocol (American Nuclear Society 1986) the test specimens were leached in a set volume of tap water (volume = 10 times the specimen surface area (cm^2) in milliliters; e.g., 100 cm^2 surface area leached in 1 L of leachant). At various time periods from the start of the test the solution was completely exchanged with fresh solution. This was accomplished by placing the test specimen in a new bottle filled with tap water. The leached radionuclides, nitrate, pH, and alkalinity of the resultant solutions were measured on each sample exchange. The solution exchange times were 3, 7, 14, 21, 35, 56, and 84 days. After each leach period the leach containers were also rinsed with a small volume of dilute nitric acid to assure no contaminants had adsorbed onto the container walls. If any measurable mass was found on the leach containers the mass was added to that found in solution to allow the total mass (activity) leached to be calculated.

Using the total mass leached versus cumulative time the effective diffusion coefficients and leachability indices of each contaminant were calculated following the equations and procedures detailed in ANS (1986).

Table 7 lists the starting inventory of radionuclides and nitrate in each type of grout. Actual dimensions, weights, and raw leaching data are found in the appendix.

Table 8 lists the leachability indices (LI) and cumulative effective diffusion coefficients for each type of grout after 84 days of leaching. Duplicate tests were run for each type of cement/additive/contaminant combination.

Tables 9 and 10 summarize the pH values measured in all the leachates. Table 9 shows the average pH value for each leachate averaged over all seven samplings. Table 10 shows the average pH value of each sampling's leachate regardless of grout formulation. Total alkalinity measurements (data not presented) of the leachates show very similar trends to the pH data.

TABLE 8. Leach Results After 84 Days of Leaching

Grout		Contaminant					
	Leach Parameter	TeO_4^-	CrO_4^{2-}	Cs^+	SeO_4^{2-}	Sr^{2+}	NO_3^-
Control	LI ^(a)	8.3±0.2	10.4±1.2	8.3±0.3	9.2±0.3	10.7±0.4	8.4±0.2
	LI	8.2±0.3	9.4±0.3	8.1±0.4	8.8±0.6	10.6±0.4	8.0±0.3
	D_{cum} ^(b)	7.0×10^{-9}	7.9×10^{-11}	5.8×10^{-9}	6.3×10^{-10}	1.9×10^{-11}	5.1×10^{-9}
	D_{cum}	8.3×10^{-9}	1.5×10^{-10}	1.0×10^{-8}	1.8×10^{-9}	2.6×10^{-11}	1.3×10^{-8}
FeS	LI	10.6±0.2	9.9±0.3	8.3±0.5	8.2±0.2	10.4±0.3	7.4±0.5
	LI	10.7±0.2	10.0±0.3	8.5±0.5	8.3±0.2	10.5±0.3	7.4±0.4
	D_{cum}	2.6×10^{-11}	1.1×10^{-10}	3.1×10^{-9}	8.8×10^{-9}	4.3×10^{-11}	1.9×10^{-7}
	D_{cum}	2.1×10^{-11}	1.0×10^{-10}	4.7×10^{-9}	6.2×10^{-9}	3.5×10^{-11}	1.9×10^{-7}
Pebble Phosphate	LI	7.6±0.4	9.5±0.3	8.7±0.4	8.2±0.2	10.7±0.3	7.5±0.4
	LI	7.5±0.4	9.4±0.2	8.9±0.4	8.2±0.1	10.7±0.3	7.4±0.4
	D_{cum}	9.1×10^{-8}	4.2×10^{-10}	1.9×10^{-9}	7.8×10^{-9}	2.0×10^{-11}	1.5×10^{-7}
	D_{cum}	1.4×10^{-7}	4.5×10^{-10}	1.3×10^{-9}	8.3×10^{-9}	2.1×10^{-11}	1.9×10^{-7}
Clinoptilolite	LI	7.7±0.8	8.8±0.6	9.7±0.4	7.9±0.1	10.8±0.4	7.8±1.1
	LI	7.9±1.0	8.9±0.5	9.8±0.3	7.9±0.1	10.8±0.3	7.8±1.2
	D_{cum}	1.9×10^{-7}	4.4×10^{-9}	1.8×10^{-10}	2.2×10^{-8}	1.5×10^{-11}	6.8×10^{-8}
	D_{cum}	7.6×10^{-8}	2.1×10^{-9}	1.7×10^{-10}	1.9×10^{-8}	1.4×10^{-11}	1.2×10^{-7}
Mixed Bed Ion Exchange	LI	11.0±0.3	9.4±0.5	7.8±0.4	9.1±0.5	10.5±0.4	8.2±0.4
	LI	10.9±0.1	9.8±0.2	7.8±0.4	9.0±0.4	10.4±0.2	7.9±0.4
	D_{cum}	1.2×10^{-11}	3.8×10^{-10}	2.9×10^{-8}	1.1×10^{-9}	3.0×10^{-11}	9.3×10^{-9}
	D_{cum}	8.4×10^{-12}	1.4×10^{-10}	3.2×10^{-8}	1.2×10^{-9}	4.0×10^{-11}	2.4×10^{-8}
Mixed Metal Oxide	LI	7.9±0.9	9.7±0.4	9.3±0.6	9.2±0.6	11.5±0.5	7.7±0.8
	LI	8.0±0.8	9.6±0.5	8.7±0.4	9.2±0.5	11.7±0.3	8.1±0.8
	D_{cum}	4.9×10^{-8}	2.2×10^{-10}	7.8×10^{-10}	9.5×10^{-10}	3.4×10^{-12}	7.6×10^{-8}
	D_{cum}	2.7×10^{-8}	3.4×10^{-10}	1.9×10^{-9}	8.0×10^{-10}	2.0×10^{-12}	2.0×10^{-8}

(a) LI = leachability index (unitless) $\sum_{t=0}^t -\log D_{\text{inc}}$

(b) D_{cum} = cumulative effective diffusion coefficient (cm^2/s)

TABLE 9. Average Leachate pH Values Over Seven Sampling Times

<u>Grout Formulation</u>	<u>pH</u>
Control	11.12±0.18
FeS	11.23±0.17
Pebble Phosphate	11.24±0.16
Clinoptilolite	11.24±0.32
Mixed Bed Ion Exchange	11.46±0.13
Mixed Metal Oxide	11.54±0.21

TABLE 10. Average Leachate pH Values For All Grouts

<u>Sample Time (d)</u>	<u>pH</u>
3	11.53±0.41
7	11.39±0.20
14	11.34±0.21
21	11.20±0.18
35	11.27±0.12
56	11.28±0.12
84	11.14±0.17

DISCUSSION OF LEACH RESULTS

In general, cementitious waste forms do not readily sequester anionic and alkali metal ions. To improve the retention of these types of ions specific additives are often used. Table 8 shows that none of the reagents chosen in this study improve the retention of nitrate. In fact, most of the cement formulations with additives allow nitrate to leach faster than the control formulation.

Pertechnetate (TcO_4^-) anion leaches fairly rapidly from the control cement formulation. The additives clinoptilolite and Florida pebble phosphate (fluorapatite) have a detrimental effect on Tc sequestering. The available leach tests do not allow us to determine whether the additives compromise the waste form physical structure (porosity, mean pore size, tortuosity) or the waste form pore water chemistry (release competing ions such as PO_4^{3-} to compete for adsorption sites on cement/fly ash hydration products). The additives FeS and mixed bed exchange resin improve the leach resistance of the grouts for TcO_4^- very dramatically. FeS likely reduces TcO_4^- to lower valence states Tc (III, IV) that form insoluble oxides in the waste form pores. The mixed bed exchange resin likely adsorbs the TcO_4^- anion and retards its release from the solidified waste. The mixed metal oxide anion getter appears to slightly impede the retention of TcO_4^- versus the control formulation. mixed metal oxide is less efficient at sequestering monovalent anions than divalent anions.

Cesium leaches quite rapidly from the control cement formulation. The formulation using FeS additive does not appear to affect Cs leaching. The Amberlite mixed-bed exchange resin grout formulation appears to increase the rate of cesium leaching. Apparently the cation portion of the mixed-bed exchange resin is completely overwhelmed by the high sodium content of the DSSF waste liquid and adsorption of cesium is minimal. The replacement of some cement and fly ash with exchange resin likely compromises some of the physical attributes of the solid waste form thus increasing the leaching of soluble constituents such as Cs^+ present in the waste form pores. The addition of mixed metal oxide and pebble phosphate to the grout helps sequester cesium ions compared to the control cement. The exact mechanism is

not apparent because neither additive is expected to be a strong adsorbent for monovalent cations. The formulation using clinoptilolite greatly improves the sequestering of cesium. The zeolite, clinoptilolite, is a well-known highly selective adsorbent for cesium.

The selenate anion, SeO_4^{2-} , is held moderately well by the control formulation. The clinoptilolite additive has a deleterious effect on selenate leaching perhaps because of compromised physical structure (greater porosity and pore sizes). The additives pebble phosphate and FeS grout formulations also show slightly increased SeO_4^{2-} leaching. The mixed bed IEX and mixed metal oxide do not affect or very slightly improve the leaching characteristics of the selenate despite the fact that both should readily adsorb anions. The large mass of competing anions in the DSSF liquid waste may overwhelm the exchange capacity of these exchangers.

The control formulation sequesters CrO_4^{2-} better than any of the formulations with additives. It is unclear what mechanism causes the retention of CrO_4^{2-} within cement/fly ash hydration products but similar low leach rates are observed for CrO_4^{2-} in various Hanford liquid waste-grout studies (Serne and Wood 1990). The grouts with the FeS, mixed bed IEX, and mixed metal oxide additives show very small increases in CrO_4^{2-} leach rates. Clinoptilolite substituted grout allows significant CrO_4^{2-} leaching. The clinoptilolite grout allows significantly more leaching of every anion studied perhaps because its presence increases waste form porosity/pore sizes.

All the cementitious waste forms retain Sr^{2+} quite strongly. After 84 days, leaching of the relatively small waste forms only 2.4% of the Sr leaches versus 45% to 100% of the nitrate. Interestingly, the grout with the mixed metal oxide anion-getting additive leaches the least Sr. This improved retention of the cation Sr by this product is unexplained.

No additive greatly enhances the leach resistance of the cement for all five common and important contaminants. For specific contaminants a specific additive may show good improvement over the control formulation. Cesium retention is improved by many of the additives. None of the additives appear to significantly improve the leach resistance of NO_3^- , CrO_4^{2-} , or SeO_4^{2-} . Clinoptilolite and pebble phosphate appear to have significant detrimental effects on anion leaching.

The pH of the diluted DSSF waste liquid and cement pore waters is quite high. The resultant leachates from contacting the specimens with tap water at a ratio of 10 mL for each 1-cm² surface area show alkaline pH values from 11.1 to 11.5. The highest pH values are found for grouts with mixed bed IEX and mixed metal oxide, both of which release OH⁻ upon adsorbing other anions. The raw data in the appendix show leaching occurs most rapidly at the very beginning of the tests and then slowly diminishes. One can thus imply that the additives are not rapidly breaking down in the first 84 days, but these tests do not address long-term performance.

These preliminary data for one waste type, six representative contaminants, and five potential additives do not identify one additive as clearly superior for the range of contaminants studied. Without further work it is impossible to determine whether the additives that increase leaching do so by compromising physical structure or the chemical environment within the pores. More detailed solids analyses for porosity, pore size, and pore connectivity would be needed to look for changes in physical structure.

Other additives such as activated carbon and synthetic zeolites could be studied. A wider range of contaminant types, such as sludges, contaminated soils, and hazardous organic compounds, could also be studied to build a large data bank from which waste specific grout formulations could be chosen for each specific field site that is considered for in situ stabilization.

The present study has identified ¹³⁷Cs and ⁹⁹Tc as two contaminants for which an additive could greatly increase the leach resistance of the standard injectable grout. The user should characterize the wastes present in the field disposal unit, rank the contaminants' long-term hazard potential, and choose additives to improve the leach resistance of the contaminants that exhibit larger potential hazards. Before finalizing the additive choice the operator should consider whether the additive would deleteriously affect the leach resistance of other high-risk contaminants also present in the disposal unit. Systems performance assessments using leach data, site-specific soil, hydrologic, and release scenarios can be performed to develop an objective cost-benefits analyses of various grout injection remediation schemes.

REFERENCES

- American Nuclear Society (ANS). 1986. Measurement of the Leachability of Solidified Low-Level Radioactive Wastes by a Short-Term Test Procedure. ANSI/ANS 16.1-1986, American Nuclear Society, LaGrange Park, Illinois.
- American Society for Testing and Materials. 1985. "Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens, Method C39-84." In Annual Book of Standards Vol 04.02 Concrete and Mineral Aggregates, pp.24-29. ASTM Publishing, Philadelphia.
- Ames, L. L. 1960. "The Cation Sieve Properties of Clinoptilolite." Am. Mineral. 45:689-700.
- Early, T. V., D. R. Dreives, G. K. Jacobs, and R. C. Routson. 1982. Geochemical Controls on Radionuclide Releases from a Nuclear Waste Repository in Basalt: Estimated Solubilities for Selected Elements. RHO-BW-ST-39P, Rockwell Hanford Operations, Richland, Washington.
- Hay, R. L. 1963. "Stratigraphy and Zeolitic Diagenesis of the John Day Formation of Oregon." Calif. Univ. Publ. Geol. Sci. 42:199-262.
- Hay, R. L. 1978. "Geologic Occurrences of Zeolites." In Natural Zeolites, eds. L. B. Sand and F. A. Mumpton, pp. 135-144. Pergamon Press, Oxford.
- Matsuzuru, H., and A. Ito. 1977. "Immobilization of Cesium-137 in Cement Waste Composites by Addition of Mineral Zeolites." Health Phys. 34:643-648.
- McClelland, G. H., and J. R. Lehr. 1969. "Crystal-Chemical Investigation of Natural Apatites." Am. Mineral. 54:1374-1391.
- Mumpton, F. A. 1977. "Utilization of Natural Zeolites." In Mineralogy and Geology of Natural Zeolites. Vol. 4, pp. 177-204. Mineral. Soc. Amer. Short Course Notes, Mineralogy Society of America, Washington DC.
- Phillips, S. J., J. W. Cammann, H. L. Benny, R. J. Serne, P. F. Martin, and L. L. Ames. 1992. "Development, Testing, and Demonstration of Geotechnical Equipment and Cement-Based Encapsulant Materials for the Stabilization of Radioactive and Hazardous Waste Disposal Structures." Presented at Fourth International Conference on the Use of Fly Ash, Silica Fume, Slag, and Natural Pozzolans in Concrete, Istanbul, Turkey, May 3-8, 1992. WHC-SA-1039-FP, Westinghouse Hanford Company, Richland, Washington.
- Reisenauer, A. E., and L. L. Ames. 1961. Removal and Recovery of Plutonium from 234-5 Building Sump Waste with Phosphate Rock. HW-70041, General Electric, Richland, Washington.
- Serne, R. J., and M. I. Wood. 1990. Hanford Waste-Form Release and Sediment Interaction--A Status Report with Rationale and Recommendations for Additional Studies. PNL-7297, Pacific Northwest Laboratory, Richland, Washington.
- Thornber, M. R. 1983. "Weathering of Sulphide Bodies." In Geochemical Exploration in Deeply Weathered Terrain, ed. R. E. Smith, pp. 67-76, 92-103. CSIRO, Floreat Park, W. A., Australia.

APPENDIX

DETAILS ON SPECIMEN SIZE AND ANS 16.1 LEACH TESTS

APPENDIX

DETAILS ON SPECIMEN SIZE AND ANS 16.1 (LEACH TESTS)

Table A.1 presents the dimensions of each test specimen and the calculated volume to surface area ratio. The latter is a direct input to the equation used to calculate effective diffusion coefficients. Table A.1 also lists the codes used to designate which additive was placed in each test specimen.

The tables following Table A.1 are printouts of the important variables for each leach test that are needed to calculate the effective diffusion coefficients. From these tables one can independently check our calculations or evaluate leaching using another approach. The tables contain a header that identifies the contaminant being studied and additive included in the sample. Each table consists of eight columns. The first column specifies the sample number and leach interval, the second column lists the measured amount of

TABLE A.1. ANS 16.1 Leach Sample Dimensions^(a)

<u>Gamma-Emitter Spiked</u>				<u>Technetium Spiked</u>			
<u>Sample</u>	<u>Height (mm)</u>	<u>Weight (g)</u>	<u>V/SA (cm)</u>	<u>Sample</u>	<u>Height (mm)</u>	<u>Weight (g)</u>	<u>V/SA (cm)</u>
A-1	40.64	57.77	0.571	A-1	39.37	57.02	0.566
A-2	39.37	54.28	0.566	A-2	40.39	57.97	0.570
B-1	41.66	76.06	0.575	B-1	39.62	72.59	0.567
B-2	39.62	76.20	0.567	B-2	42.67	81.72	0.579
C-1	42.42	63.95	0.578	C-1	40.13	60.96	0.569
C-2	39.37	59.51	0.566	C-2	40.64	59.82	0.571
D-1	40.39	52.51	0.570	D-1	41.40	54.68	0.574
D-2	40.39	52.82	0.570	D-2	39.88	52.20	0.568
E-1	39.62	49.55	0.567	E-1	40.39	51.85	0.570
E-2	39.88	51.63	0.568	E-2	40.89	51.82	0.572
F-1	38.10	53.15	0.560	F-1	39.37	52.84	0.566
F-2	36.07	49.20	0.551	F-2	39.88	53.44	0.568

(a) All sample diameters = 31.75 mm

A = Control, B = FeS, C = Florida Pebble Phosphate,

D = Clinoptilolite, E = mixed bed IEX, F = mixed metal oxide

contaminant (A_n) in each leach solution and the third column provides the cumulative amount leached (Σa_n) from the waste form up through the current leach interval. The fourth column tabulates the cumulative time of leaching in days. The fifth and sixth columns list the ratio of the amount of contaminant leached in each interval to the total inventory of contaminant in the grout specimen and the ratio of the cumulative amount of contaminant leached over all intervals through the current leach interval, respectively. Columns seven and eight list the incremental effective diffusion coefficient and cumulative effective diffusion coefficient for the contaminant. The incremental diffusion coefficient corresponds to the amount leached in each leach interval while the cumulative diffusion coefficient corresponds to the total amount of contaminant leached from the beginning of the test up through the current leach interval. More details on the significance of these data can be found in ANS (1986).

TABLE 1991-INSITU-A1C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC A-1-1	0.09	0.09	3	6.54e-02	6.54e-02	4.21e-09	4.21e-09
" " 2	0.07	0.16	7	4.94e-02	1.15e-01	8.63e-09	5.56e-09
" " 3	0.08	0.24	14	5.44e-02	1.69e-01	7.28e-09	1.16e-08
" " 4	0.06	0.30	21	4.04e-02	2.10e-01	6.81e-09	7.00e-09
" " 5	0.09	0.38	35	6.09e-02	2.71e-01	6.16e-09	7.23e-09
" " 6	0.10	0.48	56	6.76e-02	3.38e-01	5.49e-09	7.60e-09
" " 7	0.07	0.55	84	4.77e-02	3.86e-01	2.37e-09	6.96e-09

TABLE 1991-INSITU-A21C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC A-2-1	0.16	0.16	3	1.09e-01	1.09e-01	1.18e-08	1.18e-08
" " 2	0.07	0.23	7	5.25e-02	1.62e-01	9.75e-09	1.10e-08
" " 3	0.08	0.31	14	5.87e-02	2.21e-01	8.46e-09	1.16e-08
" " 4	0.06	0.38	21	4.25e-02	2.63e-01	7.55e-09	1.11e-08
" " 5	0.09	0.47	35	6.39e-02	3.27e-01	6.77e-09	1.14e-08
" " 6	0.09	0.56	56	6.26e-02	3.90e-01	4.71e-09	1.04e-08
" " 7	0.05	0.60	84	3.26e-02	4.22e-01	1.11e-09	8.29e-09

TABLE 1991-INSITU-B1C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC B-1-1	0.01	0.01	3	6.17e-03	6.17e-03	3.70e-11	3.70e-11
" " 2	0.00	0.01	7	1.98e-03	8.14e-03	1.36e-11	2.77e-11
" " 3	0.00	0.02	14	3.45e-03	1.16e-02	2.89e-11	2.80e-11
" " 4	0.00	0.02	21	1.90e-03	1.35e-02	1.48e-11	2.53e-11
" " 5	0.01	0.02	35	4.42e-03	1.79e-02	3.21e-11	2.68e-11
" " 6	0.01	0.03	56	4.77e-03	2.27e-02	2.71e-11	2.68e-11

TABLE 1991-INSITU-B21C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC B-2-1	0.01	0.01	3	4.02e-03	4.02e-03	1.64e-11	1.64e-11
" " 2	0.00	0.01	7	1.59e-03	5.61e-03	9.18e-12	1.37e-11
" " 3	0.00	0.01	14	3.03e-03	8.64e-03	2.33e-11	1.62e-11
" " 4	0.00	0.02	21	2.21e-03	1.08e-02	2.09e-11	1.70e-11
" " 5	0.01	0.02	35	4.31e-03	1.52e-02	3.18e-11	2.00e-11
" " 6	0.01	0.03	56	4.39e-03	1.95e-02	2.38e-11	2.07e-11
" " 7	0.01	0.04	84	4.20e-03	2.38e-02	1.97e-11	2.06e-11

TABLE 1991-INSITU-C1TC : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC C-1-1	0.38	0.38	3	2.85e-01	2.85e-01	7.99e-08	9.92e-08
" " 2	0.11	0.49	7	8.46e-02	3.70e-01	2.52e-08	7.38e-08
" " 3	0.20	0.69	14	1.46e-01	5.16e-01	5.25e-08	8.42e-08
" " 4	0.12	0.81	21	9.04e-02	6.07e-01	3.40e-08	8.56e-08
" " 5	0.18	0.99	35	1.36e-01	7.43e-01	3.08e-08	9.03e-08
" " 6	0.15	1.14	56	1.10e-01	8.53e-01	1.44e-08	9.29e-08
" " 7	0.09	1.23	84	6.75e-02	9.20e-01	4.73e-09	9.07e-08

TABLE 1991-INSITU-C2TC : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC C-2-1	0.38	0.38	3	2.88e-01	2.88e-01	8.17e-08	9.92e-08
" " 2	0.15	0.52	7	1.11e-01	3.99e-01	4.37e-08	8.85e-08
" " 3	0.20	0.72	14	1.53e-01	5.52e-01	5.78e-08	9.67e-08
" " 4	0.12	0.84	21	9.22e-02	6.44e-01	3.56e-08	9.72e-08
" " 5	0.18	1.02	35	1.37e-01	7.81e-01	3.12e-08	1.08e-07
" " 6	0.15	1.18	56	1.17e-01	8.97e-01	1.65e-08	1.21e-07
" " 7	0.01	1.19	84	1.06e-02	9.08e-01	1.18e-10	8.53e-08

TABLE 1991-INSITU-D1TC : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC D-1-1	0.72	0.72	3	4.59e-01	4.59e-01	2.10e-07	2.89e-07
" " 2	0.22	0.94	7	1.37e-01	5.96e-01	6.76e-08	2.45e-07
" " 3	0.26	1.20	14	1.66e-01	7.62e-01	6.86e-08	2.47e-07
" " 4	0.10	1.30	21	6.40e-02	8.26e-01	1.73e-08	2.26e-07
" " 5	0.12	1.42	35	7.95e-02	9.05e-01	1.06e-08	2.05e-07
" " 6	0.14	1.57	56	9.22e-02	9.98e-01	1.04e-08	2.79e-07
" " 7	0.03	1.60	84	2.21e-02	1.02e+00	5.15e-10	1.86e-07

TABLE 1991-INSITU-D2TC : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
TC D-2-1	0.55	0.55	3	3.65e-01	3.65e-01	1.30e-07	1.72e-07
" " 2	0.24	0.79	7	1.61e-01	5.26e-01	9.07e-08	1.77e-07
" " 3	0.25	1.04	14	1.66e-01	6.92e-01	6.75e-08	1.82e-07
" " 4	0.10	1.14	21	7.00e-02	7.62e-01	2.03e-08	1.64e-07
" " 5	0.11	1.26	35	7.61e-02	8.39e-01	9.55e-09	1.42e-07
" " 6	0.04	1.30	56	2.98e-02	8.68e-01	1.06e-09	1.03e-07
" " 7	0.03	1.33	84	2.17e-02	8.90e-01	4.88e-10	7.61e-08

TABLE 1991-INSITU-E11C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec		
TC E-1-1	0.01	0.01	3	5.56e-03	5.56e-03	3.06e-11	3.06e-11		
" " 2	0.00	0.01	7	1.85e-03	7.41e-03	1.22e-11	2.33e-11		
" " 3	0.00	0.01	14	2.67e-03	1.01e-02	1.76e-11	2.16e-11		
" " 4	0.00	0.02	21	1.81e-03	1.19e-02	1.38e-11	2.00e-11		
" " 5	0.00	0.02	35	2.44e-03	1.43e-02	9.99e-12	1.74e-11		
" " 6	0.00	0.02	56	2.23e-03	1.66e-02	6.03e-12	1.46e-11		
" " 7	0.00	0.02	84	1.79e-03	1.84e-02	3.37e-12	1.19e-11		

TABLE 1991-INSITU-E21C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec		
TC E-2-1	0.00	0.00	3	3.85e-03	3.85e-03	1.47e-11	1.47e-11		
" " 2	0.00	0.01	7	1.71e-03	5.56e-03	1.04e-11	1.31e-11		
" " 3	0.00	0.01	14	2.93e-03	8.48e-03	2.12e-11	1.53e-11		
" " 4	0.00	0.01	21	1.54e-03	1.00e-02	9.92e-12	1.42e-11		
" " 5	0.00	0.02	35	2.38e-03	1.24e-02	9.49e-12	1.31e-11		
" " 6	0.00	0.02	56	1.82e-03	1.42e-02	4.02e-12	1.07e-11		
" " 7	0.00	0.02	84	1.22e-03	1.54e-02	1.56e-12	8.44e-12		

TABLE 1991-INSITU-F11C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec		
TC F-1-1	0.56	0.56	3	3.44e-01	3.44e-01	1.15e-07	1.42e-07		
" " 2	0.22	0.79	7	1.37e-01	4.80e-01	6.51e-08	1.38e-07		
" " 3	0.22	1.01	14	1.33e-01	6.14e-01	4.31e-08	1.28e-07		
" " 4	0.10	1.11	21	6.26e-02	6.76e-01	1.61e-08	1.16e-07		
" " 5	0.10	1.21	35	6.22e-02	7.38e-01	6.33e-09	9.03e-08		
" " 6	0.06	1.28	56	3.81e-02	7.77e-01	1.72e-09	6.73e-08		
" " 7	0.04	1.31	84	2.33e-02	8.00e-01	5.60e-10	4.92e-08		

TABLE 1991-INSITU-F21C : FRACTION LEACHED FOR TC-99 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec		
TC F-2-1	0.53	0.53	3	3.19e-01	3.19e-01	9.96e-08	1.24e-07		
" " 2	0.16	0.69	7	9.79e-02	4.17e-01	3.37e-08	9.95e-08		
" " 3	0.18	0.87	14	1.06e-01	5.23e-01	2.73e-08	8.42e-08		
" " 4	0.10	0.97	21	6.09e-02	5.84e-01	1.54e-08	7.44e-08		
" " 5	0.09	1.06	35	5.69e-02	6.41e-01	5.34e-09	5.83e-08		
" " 6	0.06	1.12	56	3.39e-02	6.75e-01	1.37e-09	3.83e-08		
" " 7	0.04	1.16	84	2.17e-02	6.96e-01	4.87e-10	2.67e-08		

TABLE 1991-INSITU-A1CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
CS A-1-1	0.08	0.08	3	5.91e-02	5.91e-02	3.45e-09	3.45e-09
" " 2	0.04	0.12	7	3.23e-02	9.15e-02	3.71e-09	3.54e-09
" " 3	0.10	0.22	14	7.27e-02	1.64e-01	1.30e-08	5.70e-09
" " 4	0.06	0.27	21	4.46e-02	2.09e-01	8.34e-09	7.00e-09
" " 5	0.08	0.35	35	6.04e-02	2.69e-01	6.09e-09	7.23e-09
" " 6	0.07	0.42	56	5.17e-02	3.21e-01	3.22e-09	6.63e-09
" " 7	0.05	0.47	84	3.64e-02	3.57e-01	1.39e-09	5.78e-09

TABLE 1991-INSITU-A2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
CS A-2-1	0.11	0.11	3	8.50e-02	8.50e-02	7.02e-09	7.02e-09
" " 2	0.11	0.21	7	8.76e-02	1.73e-01	2.68e-08	1.24e-08
" " 3	0.11	0.32	14	8.51e-02	2.58e-01	1.76e-08	1.67e-08
" " 4	0.07	0.39	21	5.35e-02	3.11e-01	1.18e-08	1.64e-08
" " 5	0.08	0.46	35	6.37e-02	3.75e-01	6.65e-09	1.48e-08
" " 6	0.06	0.53	56	5.05e-02	4.25e-01	3.02e-09	1.31e-08
" " 7	0.04	0.57	84	3.62e-02	4.62e-01	1.35e-09	1.03e-08

TABLE 1991-INSITU-B1CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
CS B-1-1	0.13	0.13	3	1.05e-01	1.05e-01	1.10e-08	1.10e-08
" " 2	0.07	0.21	7	5.76e-02	1.63e-01	1.20e-08	1.14e-08
" " 3	0.11	0.32	14	8.68e-02	2.49e-01	1.89e-08	1.53e-08
" " 4	0.06	0.38	21	4.72e-02	2.97e-01	9.48e-09	1.30e-08
" " 5	0.07	0.45	35	5.31e-02	3.50e-01	4.76e-09	1.04e-08
" " 6	0.05	0.50	56	3.81e-02	3.88e-01	1.78e-09	8.29e-09
" " 7	0.04	0.53	84	2.79e-02	4.16e-01	8.29e-10	3.11e-09

TABLE 1991-INSITU-B2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
CS B-2-1	0.10	0.10	3	7.99e-02	7.99e-02	6.21e-09	6.21e-09
" " 2	0.06	0.16	7	4.55e-02	1.25e-01	7.23e-09	6.56e-09
" " 3	0.09	0.25	14	7.00e-02	1.95e-01	1.19e-08	7.96e-09
" " 4	0.05	0.30	21	4.03e-02	2.36e-01	6.70e-09	9.33e-09
" " 5	0.06	0.36	35	4.45e-02	2.80e-01	3.26e-09	7.87e-09
" " 6	0.04	0.40	56	3.25e-02	3.13e-01	1.25e-09	6.17e-09
" " 7	0.03	0.43	84	1.97e-02	3.32e-01	4.03e-10	4.74e-09

TABLE 1991-INSITU-C2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CS C-1-1	0.04	0.04	3	3.30e-02	3.30e-02	1.10e-09	1.10e-09
" " 2	0.03	0.07	7	2.32e-02	5.62e-02	1.95e-09	1.37e-09
" " 3	0.06	0.13	14	4.80e-02	1.04e-01	5.83e-09	2.35e-09
" " 4	0.04	0.17	21	2.96e-02	1.34e-01	3.76e-09	2.59e-09
" " 5	0.05	0.22	35	4.00e-02	1.74e-01	2.73e-09	2.62e-09
" " 6	0.04	0.27	56	3.19e-02	2.06e-01	1.25e-09	2.29e-09
" " 7	0.03	0.29	84	2.24e-02	2.28e-01	5.40e-10	1.88e-09

TABLE 1991-INSITU-C2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CS C-2-1	0.04	0.04	3	3.00e-02	3.00e-02	8.74e-10	8.74e-10
" " 2	0.02	0.06	7	1.88e-02	4.88e-02	1.23e-09	9.89e-10
" " 3	0.05	0.11	14	4.10e-02	8.97e-02	4.07e-09	1.68e-09
" " 4	0.03	0.14	21	2.65e-02	1.16e-01	2.89e-09	1.87e-09
" " 5	0.04	0.18	35	3.45e-02	1.51e-01	1.95e-09	1.89e-09
" " 6	0.03	0.21	56	2.64e-02	1.77e-01	8.26e-10	1.63e-09
" " 7	0.02	0.24	84	1.85e-02	1.96e-01	3.54e-10	1.33e-09

TABLE 1991-INSITU-D2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CS D-1-1	0.02	0.02	3	1.31e-02	1.31e-02	1.69e-10	1.69e-10
" " 2	0.01	0.03	7	7.81e-03	2.09e-02	2.16e-10	1.84e-10
" " 3	0.02	0.05	14	1.51e-02	3.60e-02	5.58e-10	2.73e-10
" " 4	0.01	0.06	21	9.66e-03	4.56e-02	3.89e-10	2.93e-10
" " 5	0.01	0.08	35	1.06e-02	5.62e-02	1.86e-10	2.57e-10
" " 6	0.01	0.09	56	9.13e-03	6.53e-02	1.00e-10	2.25e-10
" " 7	0.01	0.10	84	6.86e-03	7.22e-02	4.91e-11	1.83e-10

TABLE 1991-INSITU-D2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CS D-2-1	0.02	0.02	3	1.25e-02	1.25e-02	1.54e-10	1.54e-10
" " 2	0.01	0.03	7	8.66e-03	2.12e-02	2.65e-10	1.89e-10
" " 3	0.02	0.05	14	1.28e-02	3.40e-02	4.05e-10	2.44e-10
" " 4	0.01	0.06	21	9.09e-03	4.31e-02	3.45e-10	2.61e-10
" " 5	0.02	0.08	35	1.13e-02	5.44e-02	2.13e-10	2.50e-10
" " 6	0.01	0.09	56	9.06e-03	6.35e-02	9.87e-11	2.13e-10
" " 7	0.01	0.10	84	6.81e-03	7.00e-02	4.42e-11	1.72e-10

TABLE 1991-INSITU-E1CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 1. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec		
CS E-1-1	0.15	0.15	3	1.31e-01	1.31e-01	1.67e-08	1.67e-08		
" " 2	0.08	0.23	7	7.38e-02	2.05e-01	1.91e-08	1.75e-08		
" " 3	0.16	0.39	14	1.37e-01	3.42e-01	4.58e-08	3.04e-08		
" " 4	0.10	0.49	21	9.04e-02	4.33e-01	3.38e-08	3.51e-08		
" " 5	0.12	0.61	35	1.03e-01	5.35e-01	1.73e-08	3.70e-08		
" " 6	0.10	0.70	56	8.37e-02	6.19e-01	8.34e-09	3.35e-08		
" " 7	0.07	0.77	84	5.82e-02	6.77e-01	3.50e-09	2.90e-08		

TABLE 1991-INSITU-E2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 2. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec		
CS E-2-1	0.16	0.16	3	1.32e-01	1.32e-01	1.71e-08	1.71e-08		
" " 2	0.09	0.25	7	7.57e-02	2.08e-01	2.01e-08	2.10e-08		
" " 3	0.17	0.42	14	1.46e-01	3.54e-01	5.19e-08	3.24e-08		
" " 4	0.11	0.53	21	9.36e-02	4.47e-01	3.64e-08	3.91e-08		
" " 5	0.13	0.66	35	1.07e-01	5.55e-01	1.90e-08	3.87e-08		
" " 6	0.10	0.75	56	8.26e-02	6.37e-01	8.15e-09	3.65e-08		
" " 7	0.07	0.83	84	6.18e-02	6.99e-01	3.96e-09	3.17e-08		

TABLE 1991-INSITU-F1CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 1. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec		
CS F-1-1	0.09	0.09	3	5.88e-02	5.88e-02	3.29e-09	3.29e-09		
" " 2	0.04	0.13	7	2.77e-02	8.65e-02	2.61e-09	3.05e-09		
" " 3	0.06	0.19	14	4.30e-02	1.29e-01	4.38e-09	3.41e-09		
" " 4	0.04	0.23	21	2.92e-02	1.59e-01	3.43e-09	3.42e-09		
" " 5	0.04	0.27	35	2.86e-02	1.87e-01	1.31e-09	2.85e-09		
" " 6	0.00	0.27	56	2.54e-05	1.87e-01	7.50e-16	1.78e-09		
" " 7	0.00	0.27	84	2.54e-05	1.87e-01	6.52e-16	1.19e-09		

TABLE 1991-INSITU-F2CS : FRACTION LEACHED FOR CS-137 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 2. (ANS TEST IN TAP WATER)									
SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec		
CS F-2-1	0.09	0.09	3	6.30e-02	6.30e-02	3.77e-09	3.77e-09		
" " 2	0.04	0.13	7	2.84e-02	9.14e-02	2.76e-09	3.40e-09		
" " 3	0.06	0.20	14	4.44e-02	1.36e-01	4.68e-09	3.76e-09		
" " 4	0.04	0.24	21	3.07e-02	1.66e-01	3.79e-09	3.76e-09		
" " 5	0.04	0.28	35	3.02e-02	1.97e-01	1.46e-09	3.15e-09		
" " 6	0.03	0.32	56	2.22e-02	2.19e-01	5.73e-10	2.44e-09		
" " 7	0.03	0.34	84	1.92e-02	2.38e-01	3.72e-10	1.92e-09		

TABLE 1991-INSITU-A1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	Au/Ao	cum Au/Ao	D inc. cm2/sec	D cum cm2/sec
CR A-1-1	0.03	0.03	3	1.27e-02	1.27e-02	1.59e-10	1.59e-10
" " 2	0.02	0.04	7	7.65e-03	2.03e-02	2.08e-10	1.75e-10
" " 3	0.01	0.05	14	3.67e-03	2.40e-02	3.32e-11	1.22e-10
" " 4	0.02	0.06	21	7.65e-03	3.16e-02	2.45e-10	1.41e-10
" " 5	0.02	0.08	35	7.65e-03	3.93e-02	9.76e-11	1.31e-10
" " 6	0.02	0.10	56	7.65e-03	4.69e-02	7.06e-11	1.17e-10
" " 7	0.00	0.10	84	2.64e-04	4.72e-02	7.29e-14	7.86e-11

TABLE 1991-INSITU-A2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	Au/Ao	cum Au/Ao	D inc. cm2/sec	D cum cm2/sec
CR A-2-1	0.04	0.04	3	1.82e-02	1.82e-02	3.23e-10	3.23e-10
" " 2	0.02	0.05	7	8.00e-03	2.62e-02	2.23e-10	2.86e-10
" " 3	0.02	0.07	14	8.00e-03	3.42e-02	1.55e-10	2.44e-10
" " 4	0.02	0.08	21	8.00e-03	4.22e-02	2.64e-10	2.48e-10
" " 5	0.02	0.10	35	8.00e-03	5.03e-02	1.05e-10	2.10e-10
" " 6	0.02	0.11	56	8.00e-03	5.83e-02	7.59e-11	1.76e-10
" " 7	0.02	0.13	84	8.00e-03	6.63e-02	6.59e-11	1.52e-10

TABLE 1991-INSITU-B1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	Au/Ao	cum Au/Ao	D inc. cm2/sec	D cum cm2/sec
CR B-1-1	0.02	0.02	3	7.98e-03	7.98e-03	6.38e-11	6.38e-11
" " 2	0.02	0.03	7	7.98e-03	1.60e-02	2.29e-10	1.09e-10
" " 3	0.02	0.05	14	7.98e-03	2.39e-02	1.59e-10	1.23e-10
" " 4	0.02	0.06	21	7.98e-03	3.19e-02	2.71e-10	1.46e-10
" " 5	0.02	0.08	35	7.98e-03	3.99e-02	1.08e-10	1.37e-10
" " 6	0.02	0.10	56	7.98e-03	4.79e-02	7.79e-11	1.23e-10
" " 7	0.02	0.11	84	7.98e-03	5.59e-02	6.77e-11	1.12e-10

TABLE 1991-INSITU-B2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (Au)	CUM. LEACH	TIME DAYS	Au/Ao	cum Au/Ao	D inc. cm2/sec	D cum cm2/sec
CR B-2-1	0.02	0.02	3	7.69e-03	7.69e-03	5.77e-11	5.77e-11
" " 2	0.02	0.03	7	7.69e-03	1.54e-02	2.07e-10	9.89e-11
" " 3	0.02	0.05	14	7.69e-03	2.31e-02	1.44e-10	1.11e-10
" " 4	0.02	0.06	21	7.69e-03	3.08e-02	2.45e-10	1.32e-10
" " 5	0.02	0.08	35	7.69e-03	3.85e-02	9.73e-11	1.24e-10
" " 6	0.02	0.09	56	7.69e-03	4.62e-02	7.04e-11	1.11e-10
" " 7	0.02	0.11	84	7.69e-03	5.39e-02	6.12e-11	1.01e-10

TABLE 1991-INSITU-C1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR C-1-1	0.03	0.03	3	1.37e-02	1.37e-02	1.91e-10	1.91e-10
" " 2	0.01	0.04	7	7.25e-03	2.10e-02	1.91e-10	1.91e-10
" " 3	0.02	0.06	14	8.14e-03	2.91e-02	1.68e-10	1.84e-10
" " 4	0.02	0.08	21	8.39e-03	3.75e-02	3.02e-10	2.03e-10
" " 5	0.04	0.11	35	1.93e-02	5.68e-02	6.34e-10	2.80e-10
" " 6	0.05	0.17	56	2.56e-02	8.23e-02	8.08e-10	3.68e-10
" " 7	0.05	0.22	84	2.56e-02	1.08e-01	7.01e-10	4.21e-10

TABLE 1991-INSITU-C2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR C-2-1	0.03	0.03	3	1.60e-02	1.60e-02	2.50e-10	2.50e-10
" " 2	0.02	0.05	7	8.54e-03	2.46e-02	2.54e-10	2.52e-10
" " 3	0.03	0.08	14	1.69e-02	4.15e-02	6.90e-10	3.58e-10
" " 4	0.01	0.09	21	7.60e-03	4.91e-02	2.38e-10	3.34e-10
" " 5	0.03	0.13	35	1.77e-02	6.68e-02	5.13e-10	3.71e-10
" " 6	0.04	0.17	56	2.34e-02	9.01e-02	6.48e-10	4.22e-10
" " 7	0.04	0.21	84	2.34e-02	1.13e-01	5.62e-10	4.47e-10

TABLE 1991-INSITU-D1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR D-1-1	0.05	0.05	3	2.33e-02	2.33e-02	5.33e-10	5.33e-10
" " 2	0.05	0.10	7	2.41e-02	4.74e-02	2.06e-09	9.48e-10
" " 3	0.04	0.14	14	1.77e-02	6.51e-02	7.73e-10	8.95e-10
" " 4	0.03	0.17	21	1.38e-02	7.89e-02	7.95e-10	8.76e-10
" " 5	0.06	0.23	35	2.66e-02	1.06e-01	1.17e-09	9.40e-10
" " 6	0.07	0.30	56	3.35e-02	1.39e-01	1.35e-09	1.02e-09
" " 7	0.38	0.68	84	1.77e-01	3.16e-01	3.26e-08	4.42e-09

TABLE 1991-INSITU-D2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR D-2-1	0.05	0.05	3	2.18e-02	2.18e-02	4.67e-10	4.67e-10
" " 2	0.04	0.09	7	1.91e-02	4.09e-02	1.29e-09	7.04e-10
" " 3	0.03	0.12	14	1.40e-02	5.49e-02	4.83e-10	6.35e-10
" " 4	0.03	0.15	21	1.34e-02	6.83e-02	7.54e-10	6.56e-10
" " 5	0.05	0.20	35	2.41e-02	9.24e-02	9.63e-10	7.20e-10
" " 6	0.09	0.30	56	4.33e-02	1.36e-01	2.26e-09	9.71e-10
" " 7	0.22	0.51	84	9.86e-02	2.34e-01	1.01e-08	2.13e-09

TABLE 1991-INSITU-E1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR E-1-1	0.04	0.04	3	2.52e-02	2.52e-02	6.21e-10	6.21e-10
" " 2	0.03	0.08	7	1.80e-02	4.33e-02	1.14e-09	7.82e-10
" " 3	0.02	0.10	14	1.22e-02	5.55e-02	3.65e-10	6.43e-10
" " 4	0.02	0.12	21	1.18e-02	6.73e-02	5.76e-10	6.31e-10
" " 5	0.04	0.16	35	2.05e-02	8.78e-02	6.91e-10	6.44e-10
" " 6	0.02	0.17	56	8.72e-03	9.65e-02	9.04e-11	4.86e-10
" " 7	0.02	0.19	84	8.72e-03	1.05e-01	7.85e-11	3.85e-10

TABLE 1991-INSITU-E2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR E-2-1	0.02	0.02	3	1.27e-02	1.27e-02	1.58e-10	1.58e-10
" " 2	0.02	0.04	7	8.51e-03	2.12e-02	2.55e-10	1.89e-10
" " 3	0.02	0.05	14	8.51e-03	2.97e-02	1.77e-10	1.85e-10
" " 4	0.02	0.07	21	8.51e-03	3.83e-02	3.00e-10	2.04e-10
" " 5	0.02	0.09	35	8.51e-03	4.68e-02	1.19e-10	1.83e-10
" " 6	0.02	0.10	56	8.51e-03	5.53e-02	8.65e-11	1.60e-10
" " 7	0.02	0.12	84	8.51e-03	6.38e-02	7.51e-11	1.42e-10

TABLE 1991-INSITU-F1CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR F-1-1	0.04	0.04	3	1.57e-02	1.57e-02	2.33e-10	2.33e-10
" " 2	0.02	0.06	7	9.45e-03	2.51e-02	3.05e-10	2.57e-10
" " 3	0.02	0.08	14	9.63e-03	3.47e-02	2.20e-10	2.46e-10
" " 4	0.02	0.10	21	7.49e-03	4.22e-02	2.26e-10	2.42e-10
" " 5	0.02	0.12	35	1.08e-02	5.30e-02	1.87e-10	2.29e-10
" " 6	0.05	0.17	56	2.25e-02	7.55e-02	5.85e-10	2.90e-10
" " 7	0.01	0.18	84	5.58e-03	8.11e-02	3.14e-11	2.23e-10

TABLE 1991-INSITU-F2CR : FRACTION LEACHED FOR CR-51 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
CR F-2-1	0.04	0.04	3	1.96e-02	1.96e-02	3.55e-10	3.55e-10
" " 2	0.06	0.10	7	2.94e-02	4.91e-02	2.86e-09	9.49e-10
" " 3	0.03	0.13	14	1.24e-02	6.15e-02	3.53e-10	7.45e-10
" " 4	0.01	0.14	21	5.95e-03	6.74e-02	1.38e-10	5.97e-10
" " 5	0.02	0.16	35	1.15e-02	7.90e-02	2.07e-10	4.92e-10
" " 6	0.03	0.20	56	1.56e-02	9.45e-02	2.72e-10	4.40e-10
" " 7	0.01	0.21	84	6.76e-03	1.01e-01	4.45e-11	3.37e-10

TABLE 1991-INSITU-A1SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE A-1-1	0.05	0.05	3	4.00e-02	4.00e-02	1.58e-09	1.58e-09
" " 2	0.02	0.06	7	1.63e-02	5.62e-02	9.38e-10	1.34e-09
" " 3	0.02	0.09	14	1.74e-02	7.36e-02	7.44e-10	1.15e-09
" " 4	0.01	0.10	21	1.07e-02	8.43e-02	4.80e-10	1.00e-09
" " 5	0.02	0.12	35	1.89e-02	1.03e-01	5.96e-10	9.02e-10
" " 6	0.02	0.14	56	1.96e-02	1.23e-01	4.64e-10	7.98e-10
" " 7	0.01	0.15	84	1.09e-02	1.34e-01	1.24e-10	6.30e-10

TABLE 1991-INSITU-A2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (CONTROL) ANS 16.1 TEST. BATCH A FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE A-2-1	0.06	0.06	3	5.83e-02	5.83e-02	3.30e-09	3.30e-09
" " 2	0.07	0.14	7	6.76e-02	1.26e-01	1.60e-08	6.60e-09
" " 3	0.03	0.16	14	2.53e-02	1.51e-01	1.55e-09	4.76e-09
" " 4	0.02	0.18	21	1.61e-02	1.67e-01	1.07e-09	3.88e-09
" " 5	0.03	0.21	35	2.39e-02	1.91e-01	9.38e-10	3.04e-09
" " 6	0.02	0.23	56	2.18e-02	2.13e-01	5.63e-10	2.36e-09
" " 7	0.02	0.25	84	1.82e-02	2.31e-01	3.41e-10	1.85e-09

TABLE 1991-INSITU-B1SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE B-1-1	0.12	0.12	3	1.05e-01	1.05e-01	1.11e-08	1.11e-08
" " 2	0.08	0.20	7	6.94e-02	1.75e-01	1.74e-08	1.31e-08
" " 3	0.05	0.25	14	4.80e-02	2.23e-01	5.76e-09	1.16e-08
" " 4	0.03	0.28	21	3.03e-02	2.53e-01	3.90e-09	1.02e-08
" " 5	0.06	0.35	35	5.47e-02	3.08e-01	5.06e-09	9.87e-09
" " 6	0.00	0.35	56	6.51e-05	3.08e-01	5.19e-15	6.17e-09
" " 7	0.00	0.35	84	6.51e-05	3.08e-01	4.51e-15	4.11e-09

TABLE 1991-INSITU-B2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (FeS) ANS 16.1 TEST. BATCH B FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE B-2-1	0.09	0.09	3	7.88e-02	7.88e-02	6.05e-09	6.05e-09
" " 2	0.06	0.15	7	5.36e-02	1.32e-01	1.01e-08	7.32e-09
" " 3	0.05	0.20	14	4.32e-02	1.76e-01	4.53e-09	6.43e-09
" " 4	0.03	0.23	21	2.89e-02	2.04e-01	3.45e-09	5.82e-09
" " 5	0.06	0.29	35	5.05e-02	2.55e-01	4.19e-09	6.13e-09
" " 6	0.06	0.35	56	5.46e-02	3.10e-01	3.55e-09	6.17e-09
" " 7	0.07	0.42	84	5.86e-02	3.68e-01	3.54e-09	6.15e-09

TABLE 1991-INSITU-CISE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C GROUT 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE C-1-1	0.05	0.05	3	4.83e-02	4.83e-02	2.36e-09	2.36e-09
" " 2	0.05	0.10	7	4.04e-02	8.87e-02	5.93e-09	3.41e-09
" " 3	0.06	0.16	14	4.97e-02	1.38e-01	6.24e-09	4.15e-09
" " 4	0.04	0.20	21	3.71e-02	1.75e-01	5.91e-09	4.45e-09
" " 5	0.08	0.28	35	7.17e-02	2.47e-01	8.77e-09	6.13e-09
" " 6	0.09	0.37	56	8.08e-02	3.28e-01	8.08e-09	7.10e-09
" " 7	0.09	0.46	84	7.77e-02	4.06e-01	6.48e-09	7.82e-09

TABLE 1991-INSITU-C2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (PEBBLE PHOSPHATE) ANS 16.1 TEST. BATCH C GROUT 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE C-2-1	0.07	0.07	3	6.31e-02	6.31e-02	3.86e-09	3.86e-09
" " 2	0.04	0.11	7	3.99e-02	1.03e-01	5.57e-09	4.41e-09
" " 3	0.05	0.16	14	5.05e-02	1.54e-01	6.19e-09	4.90e-09
" " 4	0.04	0.20	21	3.73e-02	1.91e-01	5.72e-09	5.05e-09
" " 5	0.07	0.27	35	6.72e-02	2.58e-01	7.38e-09	6.67e-09
" " 6	0.08	0.36	56	7.91e-02	3.37e-01	7.42e-09	7.60e-09
" " 7	0.08	0.44	84	8.01e-02	4.17e-01	6.61e-09	8.29e-09

TABLE 1991-INSITU-DISE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE D-1-1	0.16	0.16	3	1.28e-01	1.28e-01	1.62e-08	1.62e-08
" " 2	0.08	0.23	7	6.47e-02	1.93e-01	1.48e-08	1.57e-08
" " 3	0.08	0.32	14	6.68e-02	2.60e-01	1.10e-08	1.67e-08
" " 4	0.06	0.38	21	5.06e-02	3.10e-01	1.07e-08	1.64e-08
" " 5	0.11	0.48	35	8.76e-02	3.98e-01	1.27e-08	1.77e-08
" " 6	0.14	0.62	56	1.14e-01	5.12e-01	1.57e-08	2.00e-08
" " 7	0.14	0.76	84	1.11e-01	6.23e-01	1.29e-08	2.24e-08

TABLE 1991-INSITU-D2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (CLINOP) ANS 16.1 TEST. BATCH D FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D Inc. cm2/sec	D cum cm2/sec
SE D-2-1	0.13	0.13	3	1.08e-01	1.08e-01	1.15e-08	1.15e-08
" " 2	0.08	0.21	7	6.43e-02	1.72e-01	1.46e-08	1.25e-08
" " 3	0.08	0.29	14	6.55e-02	2.38e-01	1.05e-08	1.40e-08
" " 4	0.06	0.35	21	4.74e-02	2.85e-01	9.37e-09	1.42e-08
" " 5	0.11	0.46	35	8.70e-02	3.72e-01	1.26e-08	1.48e-08
" " 6	0.14	0.59	56	1.13e-01	4.85e-01	1.54e-08	1.81e-08
" " 7	0.13	0.72	84	1.05e-01	5.91e-01	1.16e-08	1.94e-08

TABLE 1991-INSITU-EISE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
SE E-1-1	0.07	0.07	3	7.51e-02	7.51e-02	5.49e-09	5.49e-09
" " 2	0.02	0.10	7	2.38e-02	9.89e-02	1.99e-09	4.09e-09
" " 3	0.02	0.12	14	2.10e-02	1.20e-01	1.08e-09	3.00e-09
" " 4	0.01	0.13	21	1.28e-02	1.33e-01	6.80e-10	2.45e-09
" " 5	0.02	0.15	35	1.76e-02	1.50e-01	5.08e-10	1.89e-09
" " 6	0.02	0.17	56	1.60e-02	1.66e-01	3.05e-10	1.44e-09
" " 7	0.01	0.18	84	1.33e-02	1.80e-01	1.82e-10	1.12e-09

TABLE 1991-INSITU-E2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (AMBERLITE) ANS 16.1 TEST. BATCH E FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
SE E-2-1	0.07	0.07	3	6.50e-02	6.50e-02	4.14e-09	4.14e-09
" " 2	0.03	0.10	7	2.82e-02	9.33e-02	2.80e-09	3.64e-09
" " 3	0.02	0.12	14	2.06e-02	1.14e-01	1.04e-09	2.72e-09
" " 4	0.01	0.13	21	1.41e-02	1.28e-01	8.23e-10	2.29e-09
" " 5	0.02	0.15	35	2.05e-02	1.48e-01	6.93e-10	1.85e-09
" " 6	0.02	0.17	56	1.81e-02	1.67e-01	3.90e-10	1.45e-09
" " 7	0.02	0.19	84	1.97e-02	1.86e-01	4.04e-10	1.21e-09

TABLE 1991-INSITU-F1SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 1. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
SE F-1-1	0.07	0.07	3	5.77e-02	5.77e-02	3.16e-09	3.16e-09
" " 2	0.04	0.12	7	3.43e-02	9.20e-02	4.02e-09	3.45e-09
" " 3	0.03	0.14	14	2.09e-02	1.13e-01	1.03e-09	2.59e-09
" " 4	0.02	0.16	21	1.19e-02	1.25e-01	5.73e-10	2.11e-09
" " 5	0.02	0.18	35	1.54e-02	1.40e-01	3.82e-10	1.60e-09
" " 6	0.02	0.19	56	1.29e-02	1.53e-01	1.93e-10	1.19e-09
" " 7	0.02	0.21	84	1.43e-02	1.67e-01	2.07e-10	9.52e-10

TABLE 1991-INSITU-F2SE : FRACTION LEACHED FOR SE-75 SPIKED INSITU GROUT (SORBPLUS) ANS 16.1 TEST. BATCH F FORM 2. (ANS TEST IN TAP WATER)

SAMPLE ID	TOT. LEACH (An)	CUM. LEACH	TIME DAYS	An/Ao	cum An/Ao	D inc. cm2/sec	D cum cm2/sec
SE F-2-1	0.06	0.06	3	5.07e-02	5.07e-02	2.36e-09	2.36e-09
" " 2	0.04	0.10	7	3.08e-02	8.13e-02	3.09e-09	2.60e-09
" " 3	0.03	0.12	14	2.14e-02	1.03e-01	1.05e-09	2.08e-09
" " 4	0.01	0.13	21	1.13e-02	1.14e-01	5.02e-10	1.71e-09
" " 5	0.02	0.15	35	1.45e-02	1.28e-01	3.25e-10	1.30e-09
" " 6	0.02	0.17	56	1.33e-02	1.42e-01	2.00e-10	9.91e-10
" " 7	0.02	0.19	84	1.44e-02	1.56e-01	2.02e-10	8.01e-10

STEVE PHILLIPS ANS 16.1 LEACH DIFFUSIVITY TABLES FOR N03
AUGUST 20, 1991 CW LINENMEIER
ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
A-1 INT1	1.85e+02	1.05e+02	1.05e+02	9.00e-02	9.00e-02	3	7.98e-09	7.98e-09
A-1 INT2	8.50e+01	4.81e+01	1.53e+02	4.11e-02	1.31e-01	7	5.99e-09	7.26e-09
A-1 INT3	9.70e+01	5.50e+01	2.08e+02	4.70e-02	1.78e-01	14	5.43e-09	6.70e-09
A-1 INT4	6.71e+01	3.80e+01	2.46e+02	3.25e-02	2.11e-01	21	4.40e-09	7.00e-09
A-1 INT5	1.02e+02	5.78e+01	3.04e+02	4.94e-02	2.60e-01	35	4.05e-09	6.67e-09
A-1 INT6	1.04e+02	5.92e+01	3.63e+02	5.06e-02	3.11e-01	56	3.07e-09	6.17e-09
A-1 INT7	7.79e+01	4.41e+01	4.07e+02	3.77e-02	3.48e-01	84	1.49e-09	5.07e-09

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
A-2 INT1	2.06e+02	1.17e+02	1.17e+02	9.83e-02	9.83e-02	3	9.51e-09	9.51e-09
A-2 INT2	8.69e+01	8.12e+01	1.98e+02	6.82e-02	1.66e-01	7	1.65e-08	1.17e-08
A-2 INT3	9.94e+01	9.29e+01	2.91e+02	7.81e-02	2.45e-01	14	1.50e-08	1.40e-08
A-2 INT4	6.74e+01	6.29e+01	3.54e+02	5.28e-02	2.97e-01	21	1.17e-08	1.42e-08
A-2 INT5	1.06e+02	9.91e+01	4.53e+02	8.33e-02	3.81e-01	35	1.15e-08	1.57e-08
A-2 INT6	9.75e+01	9.12e+01	5.44e+02	7.66e-02	4.57e-01	56	7.06e-09	1.47e-08
A-2 INT7	5.59e+01	5.29e+01	5.96e+02	4.37e-02	5.01e-01	84	2.00e-09	1.27e-08

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
B-1 INT1	4.22e+02	2.40e+02	2.40e+02	2.18e-01	2.18e-01	3	4.69e-08	4.90e-08
B-1 INT2	2.26e+02	2.12e+02	4.52e+02	1.92e-01	4.11e-01	7	1.31e-07	9.38e-08
B-1 INT3	2.62e+02	2.45e+02	6.97e+02	2.23e-01	6.34e-01	14	1.22e-07	1.40e-07
B-1 INT4	1.20e+02	1.12e+02	8.09e+02	1.02e-01	7.36e-01	21	4.34e-08	1.44e-07
B-1 INT5	2.09e+02	1.96e+02	1.01e+03	1.78e-01	9.14e-01	35	5.29e-08	2.05e-07
B-1 INT6	1.55e+02	1.45e+02	1.15e+03	1.32e-01	1.05e+00	56	2.09e-08	2.79e-07
B-1 INT7	8.17e+01	7.63e+01	1.23e+03	6.94e-02	1.12e+00	84	5.02e-09	1.86e-07

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
B-2 INT1	3.90e+02	2.26e+02	2.26e+02	2.01e-01	2.01e-01	3	4.11e-08	4.11e-08
B-2 INT2	1.55e+02	1.48e+02	3.74e+02	1.32e-01	3.32e-01	7	6.35e-08	5.68e-08
B-2 INT3	2.55e+02	2.45e+02	6.18e+02	2.18e-01	5.50e-01	14	1.21e-07	9.67e-08
B-2 INT4	1.11e+02	1.06e+02	7.25e+02	9.47e-02	6.45e-01	21	3.88e-08	9.72e-08
B-2 INT5	2.00e+02	1.92e+02	9.17e+02	1.71e-01	8.15e-01	35	5.01e-08	1.23e-07
B-2 INT6	1.61e+02	1.54e+02	1.07e+03	1.37e-01	9.52e-01	56	2.33e-08	1.69e-07
B-2 INT7	8.75e+01	8.35e+01	1.15e+03	7.43e-02	1.03e+00	84	5.97e-09	1.86e-07

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
C-1 INT1	3.83e+02	2.18e+02	2.18e+02	1.96e-01	1.96e-01	3	3.79e-08	3.79e-08
C-1 INT2	1.42e+02	1.26e+02	3.44e+02	1.14e-01	3.10e-01	7	4.58e-08	4.58e-08
C-1 INT3	2.44e+02	2.17e+02	5.61e+02	1.96e-01	5.06e-01	14	9.41e-08	7.62e-08
C-1 INT4	1.51e+02	1.34e+02	6.95e+02	1.20e-01	6.26e-01	21	6.04e-08	8.94e-08
C-1 INT5	2.08e+02	1.85e+02	8.80e+02	1.67e-01	7.93e-01	35	4.61e-08	1.13e-07
C-1 INT6	1.29e+02	1.14e+02	9.94e+02	1.03e-01	8.95e-01	56	1.27e-08	1.14e-07
C-1 INT7	1.07e+02	9.48e+01	1.09e+03	8.54e-02	9.81e-01	84	7.62e-09	1.54e-07

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
C-2 INT1	3.75e+02	2.13e+02	2.13e+02	1.96e-01	1.96e-01	3	3.78e-08	3.78e-08
C-2 INT2	1.82e+02	1.63e+02	3.77e+02	1.50e-01	3.46e-01	7	7.94e-08	6.08e-08
C-2 INT3	2.46e+02	2.21e+02	5.97e+02	2.02e-01	5.48e-01	14	1.01e-07	9.25e-08
C-2 INT4	1.49e+02	1.34e+02	7.31e+02	1.23e-01	6.71e-01	21	6.29e-08	1.11e-07
C-2 INT5	2.09e+02	1.88e+02	9.19e+02	1.72e-01	8.43e-01	35	4.93e-08	1.42e-07
C-2 INT6	1.62e+02	1.45e+02	1.06e+03	1.33e-01	9.77e-01	56	2.14e-08	2.04e-07
C-2 INT7	1.16e+02	1.04e+02	1.17e+03	9.55e-02	1.07e+00	84	9.52e-09	1.86e-07

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
D-1 INT1	4.47e+02	2.55e+02	2.55e+02	1.94e-01	1.94e-01	3	3.72e-08	3.72e-08
D-1 INT2	2.71e+02	2.43e+02	4.98e+02	1.86e-01	3.80e-01	7	1.22e-07	7.38e-08
D-1 INT3	3.01e+02	2.70e+02	7.68e+02	2.06e-01	5.86e-01	14	1.05e-07	1.12e-07
D-1 INT4	1.51e+02	1.35e+02	9.03e+02	1.03e-01	6.89e-01	21	4.45e-08	1.16e-07
D-1 INT5	1.89e+02	1.69e+02	1.07e+03	1.29e-01	8.19e-01	35	2.78e-08	1.23e-07
D-1 INT6	7.33e+01	6.55e+01	1.14e+03	5.00e-02	8.69e-01	56	3.01e-09	9.77e-08
D-1 INT7	1.56e+01	1.36e+01	1.15e+03	1.04e-02	8.79e-01	84	1.12e-10	6.85e-08

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
D-2 INT1	4.33e+02	2.46e+02	2.46e+02	1.97e-01	1.97e-01	3	3.82e-08	3.82e-08
D-2 INT2	2.93e+02	2.84e+02	5.30e+02	2.27e-01	4.24e-01	7	1.82e-07	9.95e-08
D-2 INT3	3.00e+02	2.90e+02	8.20e+02	2.32e-01	6.56e-01	14	1.32e-07	1.53e-07
D-2 INT4	1.60e+02	1.54e+02	9.74e+02	1.24e-01	7.79e-01	21	6.37e-08	1.72e-07
D-2 INT5	1.72e+02	1.67e+02	1.14e+03	1.33e-01	9.13e-01	35	2.95e-08	2.05e-07
D-2 INT6	5.44e+01	5.23e+01	1.19e+03	4.18e-02	9.55e-01	56	2.10e-09	1.69e-07
D-2 INT7	1.11e+01	1.03e+01	1.20e+03	8.25e-03	9.63e-01	84	7.10e-11	1.23e-07

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
E-1 INT1	2.57e+02	1.46e+02	1.46e+02	1.37e-01	1.37e-01	3	1.84e-08	1.84e-08
E-1 INT2	8.81e+01	4.99e+01	1.96e+02	4.66e-02	1.83e-01	7	7.70e-09	1.42e-08
E-1 INT3	1.45e+02	8.22e+01	2.78e+02	7.68e-02	2.60e-01	14	1.45e-08	0.00
E-1 INT4	7.56e+01	4.28e+01	3.21e+02	4.00e-02	3.00e-01	21	6.68e-09	1.53e-08
E-1 INT5	1.15e+02	6.54e+01	3.87e+02	6.11e-02	3.61e-01	35	6.21e-09	1.39e-08
E-1 INT6	8.81e+01	4.99e+01	4.37e+02	4.67e-02	4.08e-01	56	2.62e-09	1.11e-08
E-1 INT7	6.55e+01	3.70e+01	4.74e+02	3.46e-02	4.43e-01	84	1.25e-09	9.26e-09

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
E-2 INT1	2.42e+02	1.38e+02	1.38e+02	1.29e-01	1.29e-01	3	1.63e-08	1.63e-08
E-2 INT2	1.26e+02	1.18e+02	2.56e+02	1.10e-01	2.39e-01	7	4.30e-08	0.00
E-2 INT3	1.53e+02	1.43e+02	3.99e+02	1.34e-01	3.73e-01	14	4.42e-08	0.00
E-2 INT4	8.33e+01	7.79e+01	4.77e+02	7.28e-02	4.46e-01	21	2.21e-08	3.71e-08
E-2 INT5	8.94e+01	8.36e+01	5.60e+02	7.81e-02	5.24e-01	35	1.01e-08	3.37e-08
E-2 INT6	8.13e+01	7.60e+01	6.36e+02	7.10e-02	5.95e-01	56	6.06e-09	2.92e-08
E-2 INT7	5.77e+01	5.37e+01	6.90e+02	5.02e-02	6.45e-01	84	2.63e-09	2.43e-08

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
F-1 INT1	4.81e+02	2.74e+02	2.74e+02	2.00e-01	2.00e-01	3	3.93e-08	3.93e-08
F-1 INT2	3.16e+02	2.96e+02	5.70e+02	2.16e-01	4.16e-01	7	1.66e-07	9.38e-08
F-1 INT3	2.89e+02	2.72e+02	8.42e+02	1.98e-01	6.14e-01	14	9.67e-08	1.28e-07
F-1 INT4	1.46e+02	1.37e+02	9.79e+02	1.00e-01	7.15e-01	21	4.19e-08	1.32e-07
F-1 INT5	1.38e+02	1.29e+02	1.11e+03	9.43e-02	8.09e-01	35	1.48e-08	1.18e-07
F-1 INT6	8.06e+01	7.53e+01	1.18e+03	5.50e-02	8.64e-01	56	3.63e-09	9.77e-08
F-1 INT7	5.04e+01	4.69e+01	1.23e+03	3.43e-02	8.98e-01	84	1.23e-09	7.61e-08

ANS LEACH DIFF FOR N03

SAMPLE	EFF. N03	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
F-2 INT1	4.92e+02	2.80e+02	2.80e+02	2.03e-01	2.03e-01	3	4.21e-08	4.06e-08
F-2 INT2	2.72e+02	1.55e+02	4.35e+02	1.12e-01	3.15e-01	7	4.60e-08	4.93e-08
F-2 INT3	2.89e+02	1.65e+02	6.00e+02	1.19e-01	4.34e-01	14	3.62e-08	5.26e-08
F-2 INT4	1.42e+02	8.08e+01	6.80e+02	5.86e-02	4.93e-01	21	1.48e-08	4.82e-08
F-2 INT5	1.37e+02	7.80e+01	7.58e+02	5.65e-02	5.50e-01	35	5.50e-09	3.70e-08
F-2 INT6	7.96e+01	4.51e+01	8.03e+02	3.27e-02	5.82e-01	56	1.33e-09	2.79e-08
F-2 INT7	4.97e+01	2.80e+01	8.31e+02	2.03e-02	6.02e-01	84	4.46e-10	2.04e-08

STEVE PHILLIPS ANS 16.1 LEACH DIFFUSIVITY TABLES FOR N03
AUGUST 20, 1991 CW LINDERMEIER

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED		cum. An mg		An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
SAMPLE												
A-1 INT1	1.85e+02			1.05e+02		1.05e+02		9.00e-02	9.00e-02	3	7.98e-09	7.98e-09
A-2 INT2	8.50e+01			4.81e+01		1.53e+02		4.11e-02	1.31e-01	7	5.99e-09	7.26e-09
A-1 INT3	9.70e+01			5.50e+01		2.08e+02		4.70e-02	1.78e-01	14	5.43e-09	6.70e-09
A-2 INT4	6.71e+01			3.80e+01		2.46e+02		3.25e-02	2.11e-01	21	4.40e-09	7.00e-09
A-1 INT5	1.02e+02			5.78e+01		3.04e+02		4.94e-02	2.60e-01	35	4.05e-09	6.67e-09
A-2 INT6	1.04e+02			5.92e+01		3.63e+02		5.06e-02	3.11e-01	56	3.07e-09	6.17e-09
A-1 INT7	7.79e+01			4.41e+01		4.07e+02		3.77e-02	3.48e-01	84	1.49e-09	5.07e-09

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED		cum. An mg		An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
SAMPLE												
A-2 INT1	2.06e+02			1.17e+02		1.17e+02		9.83e-02	9.83e-02	3	9.51e-09	9.51e-09
A-2 INT2	8.69e+01			9.29e+01		1.98e+02		6.82e-02	1.66e-01	7	1.65e-08	1.17e-08
A-2 INT3	9.94e+01			9.29e+01		2.91e+02		7.81e-02	2.45e-01	14	1.50e-08	1.40e-08
A-2 INT4	6.74e+01			6.29e+01		3.54e+02		5.28e-02	2.97e-01	21	1.17e-08	1.42e-08
A-2 INT5	1.06e+02			9.91e+01		4.53e+02		8.33e-02	3.81e-01	35	1.15e-08	1.57e-08
A-2 INT6	9.75e+01			9.12e+01		5.44e+02		7.66e-02	4.57e-01	56	7.06e-09	1.47e-08
A-2 INT7	5.59e+01			5.20e+01		5.96e+02		4.37e-02	5.01e-01	84	2.00e-09	1.27e-08

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED		cum. An mg		An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
SAMPLE												
B-1 INT1	4.22e+02			2.40e+02		2.40e+02		2.18e-01	2.18e-01	3	4.69e-08	4.90e-08
B-1 INT2	2.26e+02			2.12e+02		4.52e+02		1.92e-01	4.11e-01	7	1.31e-07	9.38e-08
B-1 INT3	2.62e+02			2.45e+02		6.97e+02		2.23e-01	6.34e-01	14	1.22e-07	1.40e-07
B-1 INT4	1.20e+02			1.12e+02		8.09e+02		1.02e-01	7.36e-01	21	4.34e-08	1.44e-07
B-1 INT5	2.09e+02			1.96e+02		1.01e+03		1.78e-01	9.14e-01	35	5.29e-08	2.05e-07
B-1 INT6	1.55e+02			1.45e+02		1.15e+03		1.32e-01	1.05e+00	56	2.09e-08	2.79e-07
B-1 INT7	8.17e+01			7.63e+01		1.23e+03		6.94e-02	1.12e+00	84	5.02e-09	1.86e-07

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED		cum. An mg		An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
SAMPLE												
B-2 INT1	3.90e+02			2.26e+02		2.26e+02		2.01e-01	2.01e-01	3	4.11e-08	4.11e-08
B-2 INT2	1.55e+02			1.48e+02		3.74e+02		1.32e-01	3.32e-01	7	6.35e-08	5.68e-08
B-2 INT3	2.55e+02			2.45e+02		6.18e+02		2.18e-01	5.50e-01	14	1.21e-07	9.67e-08
B-2 INT4	1.11e+02			1.06e+02		7.25e+02		9.47e-02	6.45e-01	21	3.88e-08	9.72e-08
B-2 INT5	2.00e+02			1.92e+02		9.17e+02		1.71e-01	8.15e-01	35	5.01e-08	1.23e-07
B-2 INT6	1.61e+02			1.54e+02		1.07e+03		1.37e-01	9.52e-01	56	2.33e-08	1.69e-07
B-2 INT7	8.75e+01			8.35e+01		1.15e+03		7.43e-02	1.03e+00	84	5.97e-09	1.86e-07

AHS LEACH DIFF FOR N03
EFF. N03

SAMPLE	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
C-1 INT1	2.18e+02	2.18e+02	1.96e-01	1.96e-01	3	3.79e-08	3.79e-08
C-1 INT2	1.26e+02	3.44e+02	1.14e-01	3.10e-01	7	4.58e-08	4.58e-08
C-1 INT3	2.17e+02	5.61e+02	1.96e-01	5.06e-01	14	9.41e-08	7.62e-08
C-1 INT4	1.34e+02	6.95e+02	1.20e-01	6.26e-01	21	6.04e-08	8.94e-08
C-1 INT5	1.85e+02	8.80e+02	1.67e-01	7.93e-01	35	4.61e-08	1.13e-07
C-1 INT6	1.14e+02	9.94e+02	1.03e-01	8.95e-01	56	1.27e-08	1.14e-07
C-1 INT7	9.48e+01	1.09e+03	8.54e-02	9.81e-01	84	7.62e-09	1.54e-07

ANS LEACH DIFF FOR N03
EFF. N03

SAMPLE	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
C-2 INT1	2.13e+02	2.13e+02	1.96e-01	1.96e-01	3	3.78e-08	3.78e-08
C-2 INT2	1.63e+02	3.77e+02	1.50e-01	3.46e-01	7	7.94e-08	6.08e-08
C-2 INT3	2.21e+02	5.97e+02	2.02e-01	5.48e-01	14	1.01e-07	9.25e-08
C-2 INT4	1.49e+02	7.31e+02	1.23e-01	6.71e-01	21	6.29e-08	1.11e-07
C-2 INT5	1.88e+02	9.19e+02	1.72e-01	8.43e-01	35	4.93e-08	1.42e-07
C-2 INT6	1.45e+02	1.06e+03	1.33e-01	9.77e-01	56	2.14e-08	2.04e-07
C-2 INT7	1.04e+02	1.17e+03	9.55e-02	1.07e+00	84	9.52e-09	1.86e-07

ANS LEACH DIFF FOR N03
EFF. N03

SAMPLE	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
D-1 INT1	2.55e+02	2.55e+02	1.94e-01	1.94e-01	3	3.72e-08	3.72e-08
D-1 INT2	2.43e+02	4.98e+02	1.86e-01	3.80e-01	7	1.22e-07	7.38e-08
D-1 INT3	2.70e+02	7.68e+02	2.06e-01	5.86e-01	14	1.05e-07	1.12e-07
D-1 INT4	1.35e+02	9.03e+02	1.03e-01	6.89e-01	21	4.45e-08	1.16e-07
D-1 INT5	1.69e+02	1.07e+03	1.29e-01	8.19e-01	35	2.78e-08	1.23e-07
D-1 INT6	6.55e+01	1.14e+03	5.00e-02	8.69e-01	56	3.01e-09	9.77e-08
D-1 INT7	1.36e+01	1.15e+03	1.04e-02	8.79e-01	84	1.12e-10	6.85e-08

ANS LEACH DIFF FOR N03
EFF. N03

SAMPLE	mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D inc.	D cum.
D-2 INT1	2.46e+02	2.46e+02	1.97e-01	1.97e-01	3	3.82e-08	3.82e-08
D-2 INT2	2.84e+02	5.30e+02	2.27e-01	4.24e-01	7	1.82e-07	9.95e-08
D-2 INT3	2.90e+02	8.20e+02	2.32e-01	6.56e-01	14	1.32e-07	1.53e-07
D-2 INT4	1.54e+02	9.74e+02	1.24e-01	7.79e-01	21	6.37e-08	1.72e-07
D-2 INT5	1.67e+02	1.14e+03	1.33e-01	9.13e-01	35	2.95e-08	2.05e-07
D-2 INT6	5.23e+01	1.19e+03	4.18e-02	9.55e-01	56	2.10e-09	1.69e-07
D-2 INT7	1.03e+01	1.20e+03	8.25e-03	9.63e-01	84	7.10e-11	1.23e-07

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D Inc.	D cum.
SAMPLE										
E-1 INT1		2.57e+02		1.46e+02	1.46e+02	1.37e-01	1.37e-01	3	1.84e-08	1.84e-08
E-1 INT2		8.81e+01		4.99e+01	1.96e+02	4.66e-02	1.83e-01	7	7.70e-09	1.42e-08
E-1 INT3		1.45e+02		8.22e+01	2.78e+02	7.68e-02	2.60e-01	14	1.45e-08	0.00
E-1 INT4		7.56e+01		4.28e+01	3.21e+02	4.00e-02	3.00e-01	21	6.68e-09	1.53e-08
E-1 INT5		1.15e+02		6.54e+01	3.87e+02	6.11e-02	3.61e-01	35	6.21e-09	1.39e-08
E-1 INT6		8.81e+01		4.99e+01	4.37e+02	4.67e-02	4.08e-01	56	2.62e-09	1.11e-08
E-1 INT7		6.55e+01		3.70e+01	4.74e+02	3.46e-02	4.43e-01	84	1.25e-09	9.26e-09

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D Inc.	D cum.
SAMPLE										
E-2 INT1		2.42e+02		1.38e+02	1.38e+02	1.29e-01	1.29e-01	3	1.63e-08	1.63e-08
E-2 INT2		1.26e+02		1.18e+02	2.56e+02	1.10e-01	2.39e-01	7	4.30e-08	0.00
E-2 INT3		1.53e+02		1.43e+02	3.99e+02	1.34e-01	3.73e-01	14	4.42e-08	0.00
E-2 INT4		8.33e+01		7.79e+01	4.77e+02	7.28e-02	4.46e-01	21	2.21e-08	3.71e-08
E-2 INT5		8.94e+01		8.36e+01	5.60e+02	7.81e-02	5.24e-01	35	1.01e-08	3.37e-08
E-2 INT6		8.13e+01		7.60e+01	6.36e+02	7.10e-02	5.95e-01	56	6.06e-09	2.92e-08
E-2 INT7		5.77e+01		5.37e+01	6.90e+02	5.02e-02	6.45e-01	84	2.63e-09	2.43e-08

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D Inc.	D cum.
SAMPLE										
F-1 INT1		4.81e+02		2.74e+02	2.74e+02	2.00e-01	2.00e-01	3	3.93e-08	3.93e-08
F-1 INT2		3.16e+02		2.96e+02	5.70e+02	2.16e-01	4.16e-01	7	1.66e-07	9.38e-08
F-1 INT3		2.89e+02		2.72e+02	8.42e+02	1.98e-01	6.14e-01	14	9.67e-08	1.28e-07
F-1 INT4		1.46e+02		1.37e+02	9.79e+02	1.00e-01	7.15e-01	21	4.19e-08	1.32e-07
F-1 INT5		1.38e+02		1.29e+02	1.11e+03	9.43e-02	8.09e-01	35	1.48e-08	1.18e-07
F-1 INT6		8.06e+01		7.53e+01	1.18e+03	5.50e-02	8.64e-01	56	3.63e-09	9.77e-08
F-1 INT7		5.04e+01		4.69e+01	1.23e+03	3.43e-02	8.98e-01	84	1.23e-09	7.61e-08

ANS LEACH DIFF FOR N03		EFF. N03		mg LEACHED	cum. An mg	An/Ao	cum. An/Ao	TIME days	D Inc.	D cum.
SAMPLE										
F-2 INT1		4.92e+02		2.80e+02	2.80e+02	2.03e-01	2.03e-01	3	4.21e-08	4.06e-08
F-2 INT2		2.72e+02		1.55e+02	4.35e+02	1.12e-01	3.15e-01	7	4.60e-08	4.93e-08
F-2 INT3		2.89e+02		1.65e+02	6.00e+02	1.19e-01	4.34e-01	14	3.62e-08	5.26e-08
F-2 INT4		1.42e+02		8.08e+01	6.80e+02	5.86e-02	4.93e-01	21	1.48e-08	4.82e-08
F-2 INT5		1.37e+02		7.80e+01	7.58e+02	5.65e-02	5.50e-01	35	5.50e-09	3.70e-08
F-2 INT6		7.96e+01		4.51e+01	8.03e+02	3.27e-02	5.82e-01	56	1.33e-09	2.79e-08
F-2 INT7		4.97e+01		2.80e+01	8.31e+02	2.03e-02	6.02e-01	84	4.46e-10	2.04e-08

END

DATE
FILMED
7/9/93