AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

Keywords:

Replacement Tritium Facility (233-H)
Lanthanum-Nickel-Aluminum Alloy
Palladium coated Kieselguhr
Hydride Storage Bed

Retention: Permanent

**MATERIALS COMPATIBILITY OF HYDRIDE STORAGE MATERIALS
WITH AUSTENITIC STAINLESS STEELS (U)**

(NRT&SC Task No. 90-040-0)

Elliot A. Clark

Savannah River Technology Center
Equipment and Materials Technology Department
Materials Technology Section

Publication Date: 21 September 1992

D.T. Rankin 11/16/92

D.T. Rankin, Authorized Derivative Classifier

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

yes

<u>CONTENTS</u>	<u>Page</u>
Summary	1
Introduction	1
Experimental Procedures	2
Results and Discussion	4
Conclusions	5
Future Studies	5
Acknowledgments	5
Quality Assurance	5
References	7
Tables	8
Figures	11

TABLES

	<u>Page</u>
1. Exposure conditions and observations for retired prototype hydride storage beds.	8
2. Exposure conditions and observations for machined compatibility samples	9
3. Exposure conditions for cycling system samples.	10

FIGURES

	<u>Page</u>
1. Scanning electron micrograph (SEM) of interior surface of 21 Month Bed container.	11
2. Photograph of machined compatibility sample and quartz encapsulated machined compatibility sample.	12
3. Diagram of cycling systems.	13
4. Diagram of electrical and cooling air connections to each cycling system.	14
5. Variation of temperature of each tube and total system pressure with time of cycling system during cycling (typical).	15
6. SEM of unexposed and exposed Type 304 stainless steel tubes used in cycling experiments- used as received.	16
7. SEM of unexposed and exposed Type 316 stainless steel Whitey gas sample bottles used in palladium-coated kieselguhr cycling experiments.	17
8. SEM of unexposed and exposed Type 304 stainless steel tubes used in cycling experiments- annealed before exposure.	18
9. SEM of unexposed and exposed machined compatibility sample: exposed to 1500 psia hydrogen and $\text{LaNi}_{4.7}\text{Al}_{0.3}$ at 300°C. for 1 week.	19
10. SEM of exposed tube in cycling Experiment 1- exposed 686 days.	20
11. SEM of base and weld metal of interior surface of 21 Month Bed.	21
12. Photograph of unexposed and exposed machined compatibility sample.	22

APPROVALS

Elliot A. Clark Date: 11/16/92
Elliot A. Clark, Author
Materials Compatibility and Joining Group
Materials Technology Section
Equipment and Materials Technology Department/SRTC

J.R. Knight Date: 11/23/92
J.R. Knight, Customer Representative
Process Development Program
Hydrogen Technology Section
Chemical Process Technology Department/SRTC

James C. Marra Date: 11/16/92
James C. Marra, Technical Reviewer
Materials Compatibility and Joining Group
Materials Technology Section
Equipment and Materials Technology Department/SRTC

D. T. Rankin Date: 11/16/92
D.T. Rankin, Responsible Manager
Materials Compatibility and Joining Group
Materials Technology Section
Equipment and Materials Technology Department/SRTC

T.L. Capeletti Date: 11/24/92
T.L. Capeletti, Manager
Materials Technology Section
Equipment and Materials Technology Department/SRTC

**MATERIALS COMPATIBILITY OF HYDRIDE STORAGE MATERIALS WITH
AUSTENITIC STAINLESS STEEL (U)**

Elliot A. Clark

Westinghouse Savannah River Company
Savannah River Site
Aiken, SC 29808

SUMMARY

This task evaluated the materials compatibility of $\text{LaNi}_{5-x}\text{Al}_x$ ($x = 0.3, 0.75$) hydrides and palladium coated kieselguhr with austenitic stainless steel in hydrogen and tritium process environments. Based on observations of retired prototype hydride storage beds and materials exposure testing samples designed for this study, no materials compatibility problem was indicated. Scanning electron microscopy observations of features on stainless steel surfaces after exposure to hydrides are also commonly found on as-received materials before hydriding. These features are caused by either normal heat treating and acid cleaning of stainless steel or reflect the final machining operation.

INTRODUCTION

The new Building 233-H Replacement Tritium Facility will use metals and metallic compounds that form solid hydride phases extensively for storing, handling and purifying tritium¹. When a hydride forming material is cooled in the presence of a hydrogen isotope gas, the gas is absorbed by forming a hydride; in turn hydrogen gas is liberated upon heating the hydride. The various hydride compounds, in powder form, are contained in stainless steel vessels. A hydride bed is the combination of hydride powder, stainless steel container, and heating and cooling system. Hydride beds are connected to the gas handling system and will form the basis for processing tritium isotopes in Building 233-H.

A retired prototype hydride storage bed (termed the 21 Month Bed), used in tritium service, exhibited intergranular ditching on the inside surface exposed to the hydride (*Fig. 1*). Because of this observation, a program was initiated to evaluate the materials compatibility of hydrides with stainless steel². This program consisted of metallurgical analysis of stainless steel exposed to hydrides in both prototype storage and purification beds and samples exposed in small-scale experiments designed for this study. An earlier report showed that acid cleaning could cause intergranular surface ditching in Type 304L stainless steel³. This report summarizes results and conclusions of the compatibility program.

were used to adjust the power dissipated in each heater, and thus determine the maximum temperature during cycling. The variable transformers were adjusted to develop a maximum temperature of about 150° C at the end of a cycle, as measured inside the tubes during testing of the systems. Each system's pressure was measured using a pressure transducer (Omega #PX-304-050A-V).

About 1/2 atmosphere of hydrogen was introduced into each system at the beginning of each experiment. In each system at any given time, one of the hydride containing tubes was heated to decompose the hydride and evolve hydrogen gas. At the same time, the other tube was cooled by forced ambient air (controlled by an ASCO Model #8320-A172 solenoid three-way 110 VAC actuated valve) to absorb hydrogen gas by hydride formation. A timed relay (Square D Class 9050 #JCK70) automatically switched which tube was heated and cooled after a preset time; the period of switching was set on the relay. The relay provided continuous, unattended, and independent cycling of hydrogen between the tubes, resulting in long-term exposure of stainless steel to the hydride environment while cycling temperature and hydrogen. The temperature of each tube was periodically monitored using thermocouples (Omega, Type K) attached to the outside of the tubes. The thermocouples and pressure transducers were attached to a computer-controlled data acquisition system (Keithly Model 500 data acquisition with a Compaq Deskpro 286 control computer, with Labtech Notebook control software and Lotus 1-2-3 spreadsheet for data graphing and analysis). Occasional monitoring of system performance ensured proper functioning of the systems over the long exposure times used (*Fig. 5*).

A vacuum furnace at 1.6×10^{-6} Torr was used to anneal and to anneal and sensitize some of the tubes (*Table 3*). Annealed occurred at 1100° C. for 1.5 hours, and sensitization occurred at 650° C. for about 24 hours. Some tubes were oxidized by heating in air at 350°C for 40 minutes, resulting in a straw colored tinting indicative of stainless steel oxidation.

Metallurgical Evaluation

A variety of standard materials analysis techniques, including scanning electron microscopy with energy dispersive X-ray analysis, optical metallography, gas fusion analysis (to determine carbon concentrations in some samples) and visual observation were used to characterize the surface and bulk microstructure and chemical composition of samples in the three types of experiments. Samples were cut from either retired prototype beds or specially designed exposure samples, and prepared using standard metallurgical techniques appropriate for the analytical technique employed. Scanning electron microscopy and visual observation proved to be the techniques best suited to characterize stainless steel surfaces exposed to hydrides. Exposed samples were compared with identically prepared but unexposed blanks where possible, to ensure that only changes in the surface microstructure resulting from exposure to hydrides would be identified and not confused with varying initial unexposed surfaces.

RESULTS AND DISCUSSION

No evidence of a potentially adverse reaction between hydride-forming powder and stainless steel was observed in any of the exposure evaluations performed in this program. In several cases, exposed surfaces can be directly compared with unexposed surfaces (*Figs. 6, 7, 8, 9*). The hydride container surface of the longest cycle system experiment, which lasted 686 days, showed evidence of physical impregnation of the finely divided hydride powder into the surface (*Fig. 10*). Even in this case, no evidence of a potentially adverse chemical reaction was observed. Also, a machined compatibility sample was exposed to 1500 psia hydrogen at 300°C for one week exhibited no evidence of any hydride/steel interaction (*Fig. 9*). No difference in surface microstructures was observed among the variously treated tube samples (annealed, annealed and sensitized, oxidized and as received) exposed in the cycling system experiments (*Table 3*).

Some of the interior surface stainless steel microstructures had a morphology typical of the final machining process (*Figs. 6, 9*). Other surfaces exhibited intergranular ditching (*Fig. 7*) similar to the surface microstructure found in chemical test for sensitization in stainless steels⁴. It was the discovery of the intergranular surface ditched microstructure in the 21 Month Bed (*Figs. 1, 11*) that led to this study².

Optical metallography of a transverse section of the 21 Month Bed container revealed that the tube used for the container wall had been welded. Intergranular ditching appeared on both the weld and base metal surfaces (*Fig. 11*). The presence of ditching on both base and weld metal is consistent with acid cleaning to clean residual surface oxidation from the welded tube.

A previous report in this program showed that the intergranular surface ditched microstructure can be caused by acid cleaning of air annealed austenitic stainless steels³. Many of the steel parts examined, both before and after exposure, exhibit intergranular surface ditching, identical to that of the 21 Month Bed. These observations lead to the conclusion that the intergranular surface ditching found on all of these surfaces, including the 21 Month Bed, was caused by normal acid cleaning of the air annealed tubes used to fabricate the containers³.

One consistent visual observation was that both $\text{LaNi}_{4.7}\text{Al}_{0.3}$ and La_3Ni reduced or eliminated oxidation of the machined compatibility samples in several environments at elevated temperatures (*Fig. 12*). The reduction in oxidation is attributable to the highly oxidizing nature of lanthanum. This phenomena is not expected to adversely affect the operation of hydride beds in any way. Protection of stainless steel from corrosion by its oxide film is not required in the interior of hydride beds, as it would be in an aqueous corrosion environment.

CONCLUSIONS

Microstructural observations of stainless steel surfaces exposed to $\text{LaNi}_{5-x}\text{Al}_x$ ($x=0.3, 0.75$) and palladium coated kieselguhr hydrides in various environments (including air, vacuum, helium/hydrogen mixtures, 1500 psi hydrogen, cycling hydrogen, and tritium) lead to the following conclusions:

- 1) No compatibility problem exists between austenitic stainless steel containers and either $\text{LaNi}_{5-x}\text{Al}_x$ or palladium coated kieselguhr in environments similar to those in tritium processing,
- 2) The intergranular surface ditching found on the interior surfaces of retired prototype storage beds was likely caused by normal acid cleaning after air annealing during fabrication of original components of the bed vessel, and
- 3) Contact of $\text{LaNi}_{5-x}\text{Al}_x$ and La_3Ni powders with stainless steel reduced or eliminated stainless steel oxidation. This is not expected to adversely affect the performance of the hydride bed containers.

FUTURE STUDIES

Metallurgical evaluation of retired prototype tritium hydride beds will continue when samples become available. Stainless steel coupons having known surface microstructures have been and will be placed in some of these beds, to properly evaluate in service effects. The effect, if any, of intergranular surface ditching on low-cycle fatigue life of Type 316L stainless steel will be determined. Other studies underway include the effect of hydride contact on a) hydrogen permeation into stainless steel and b) the effect of hydride contact on tensile properties of Type 316L stainless steel in hydrogen. Lithium hydride contact apparently amplified the deleterious effects of hydrogen on tensile properties of stainless steel in an earlier study⁵.

ACKNOWLEDGMENTS

Technical assistance was provided by K.A. Dunn, C.L. Angerman, T. Motyka, L.K. Heung and W.C. Mosley, all of the Hydrogen Technology Section. R.R. Lathrop assisted in setting up the cycling system experiments. Metallurgical evaluation was provided by C.B. Johnson, A.S. Holston and E.E. Kemper. Quartz encapsulation was performed by D. Hopkins and D. Morgan of the SRTC Glass Shop, and other fabrication was performed by the SRTC Machine Shop. Chemical analysis was performed by the Analytical Development Section, SRTC.

QUALITY ASSURANCE

This report documents work performed under Task No. 90-040-0, "Compatibility of Stainless Steel and Hydride Storage Materials", under the Nuclear Reactor Technology and Scientific Computations

Department Quality Assurance Program, Savannah River Technology Center, Westinghouse Savannah River Company. Data used in this report is contained in laboratory notebooks DPSTN-4689, DPSTN-4773, WSRC-NB-89-203 and WSRC-89-204.

REFERENCES

1. M.S. Ortman, L.K. Heung, A. Nobile, and R.L. Rabun, III. *Tritium Processing at the Savannah River Site (SRS): Present and Future*. J. Vacuum Science and Technology A, **8**(3), pp. 2881-2889 (May/June 1990).
2. E.A. Clark. *Experimental Program Plan for Compatibility Studies of Hydride Storage Materials with Container Materials in the Replacement Tritium Facility*. USDOE Report DPST-88-667, E.I. Du Pont de Nemours & Co., Savannah River Laboratory, Aiken, SC 29808 (June 29, 1988).
3. E.A. Clark. *Formation of Intergranular Surface Ditching on Annealed Type 304L Stainless Steel by Acid Cleaning*. USDOE Report WSRC-TR-90-600, Westinghouse Savannah River Co., Savannah River Site, Aiken SC 29808 (December 1990).
4. *Standard Practice for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels*. Designation A-262-86, in "1987 Annual Book of ASTM Standards, Vol. 1.03- Steel: Plate, Sheet, Strip, Wire", American Society for Testing and Materials, Philadelphia PA, pp 67-95 (1987).
5. A.W. Thompson. *Hydrogen Embrittlement of Stainless Steels by Lithium Hydride*. Metallurgical Transactions **4**, pp 2819-2825 (December 1973).

Bed Name	Container Material	Powder	Amount of Powder (volume filled)	Gas	Cycling History	Intergranular Ditch Depth
21 Month Bed	304(L?)	LaNi _{4.7} Al ₃	80%	Tritium	1) 3 mo. cycle (per RTF), 2) 15 mo. dormant- loaded, 3) 3 mo cycle, 4) >350°C excursion in vacuum	<~ 5 μ m
Pd/K Bed	316	Pd coated Kieselguhr	>95%	Hydrogen	6 mo. cycling (per RTF) to 9000 cycles	~2 μ m
Unused Container (same type as Pd/K bed)	316	none	0	Air	none	2 μ m
T1	304(L?)	LaNi _{4.25} Al _{1.75}	~10 %	Tritium	1) D2 Activation, 2) Store ~28 month Trit loaded (3 isotherms 80°C), 3) Heat to 150°C vacuum, 4) admit air	~2 μ m
T2	304(L?)	LaNi _{4.25} Al _{1.75}	~10 %	Tritium	1) D2 Activation, 2) Store ~28 month loaded w/ Trit (3 isotherms 80°C), 3) Heat to 150° C in vacuum, 4) D2 Exchange 9X betw/ 30°-150°, 5) Accidental heat to ~350°, 6) D2 isotherms 80° & 150°, 7) Heat to 150°C in vacuum, 8) admit air	None!
TDS	304(L?)	LaNi _{4.25} Al _{1.75}	100%	Hydrogen	515°C, 81000 sec	Mainly etched flow lines, carbides (see micros)
Retired Bed	304(L?)	LaNi _{4.7} Al ₃ ?	?	Hydrogen	?	Etched carbides, slight ditching <0.5 μ m

TABLE 1. Exposure conditions (if known) and observations for retired prototype hydride storage beds.

Sample Designation	Powder Material (Batch)	Atmosphere	Temp (°C)	Time (hr)	Observations and Notes
LV1	La3Ni	vacuum	554-618	2	no tinting
LV2	La3Ni	vacuum	496	2	no tinting
GV1	LaNi4.7Al3 (T-87075)	vacuum	564	2	tinting
GV2	LaNi4.7Al3 (T-87075)	vacuum	443	2	less tinting than GV1
GV3	LaNi4.7Al3 T-87075	vacuum	566	24	no tinting
GV4	LaNi4.7Al3 T-87075	vacuum	445	24	tinting
GV5	LaNi4.7Al3 T-87075	vacuum	560	167	no tinting
GV6	LaNi4.7Al3 T-87075	vacuum	442	167	no tinting
GV7	LaNi4.7Al3 T-87075	vacuum	298	167	no tinting
GV8	LaNi4.7Al3 T-87075	vacuum	298	720	no tinting
GV9	LaNi4.7Al3 T-87075	vacuum	286	2,889	no tinting
GA1	LaNi4.7Al3 T-87075	air	544	1	oxidation
GA2	LaNi4.7Al3 T-87075	air	441	1	oxidation
GA3	LaNi4.7Al3 T-87075	air	557	2	oxidation
GA4	LaNi4.7Al3 T-87075	air	444	2	oxidation
BA1	LaNi4.7Al3 1323	air	544	1	oxidation
BA2	LaNi4.7Al3 1323	air	438	1	oxidation
BV1	LaNi4.7Al3 1323	vacuum	599	2	ampoule broke, oxidation
BV2	LaNi4.7Al3 1323	vacuum	445	2	no tinting
GI	LaNi4.7Al3	4%H2/He	548	2	tinted away from powder, clean where contact powder
G2	LaNi4.7Al3	4%H2/He	458	2	slightly tinted away from powder, clean where contact powder
G3	LaNi4.7Al3	4%H2/He	610	2	oxidized outside, clean in contact w/ powder
G4	LaNi4.7Al3	4%H2/He	649	2	oxidized outside, clean in contact w/ powder
L1	La3Ni	4%H2/He	457	2	slightly tinted away from powder, clean where contact powder
L2	La3Ni	4%H2/He	549	2	tinted away from powder, clean where contact powder
L3	La3Ni	4%H2/He	610	2	oxidized outside, clean in contact w/ powder
L4	La3Ni	4%H2/He	649	2	oxidized outside, clean in contact w/ powder
Pt. 1 blank	-	air	25	0	see notebook
LaNi4.7Al3	LaNi4.7Al3	air	25	0	see notebook
LaNi3	LaNi3	air	25	0	see notebook
air-annealed	-	air	654	2	heavy tint on top, very dark in contact w/ furnace
Hi Press H2	LaNi4.7Al3	1500 psi H2	300	168	clean, no ditching in micrographs
Pt. 2 blank	-	air	25	0	see notebook

TABLE 2. Exposure conditions and observations for machined compatibility samples.

Test	System	Tube Orientation	Cycling Period (min)	Front tube contents	Rear tube contents	Front tube condition	Rear tube condition	Total Elapsed Time (days)	Total No. Cycles
P	2	Horizontal	40	LaNi _{4.25} Al. 75	LaNi _{4.25} Al. 75	As found-unoxidized	As found-unoxidized	36	1293
1	1	Horizontal	40	LaNi _{4.25} Al. 75	LaNi _{4.25} Al. 75	cleaned	oxidized	686	24692
2	2	Horizontal	1998	LaNi _{4.25} Al. 75	LaNi _{4.25} Al. 75	cleaned	oxidized	56	40
3	3	Horizontal	40	LaNi _{4.25} Al. 75 1.5ml	LaNi _{4.25} Al. 75 1.5ml	cleaned	oxidized	36	1295
4	4	Horizontal	40	LaNi _{4.25} Al. 75 1.8ml (packed)	LaNi _{4.25} Al. 75 1.8ml (packed)	cleaned	oxidized	35	1264
5	2	Vertical	40	LaNi _{4.25} Al. 75	empty	cleaned	cleaned	98	3518
6	3	Vertical	40	LaNi _{4.25} Al. 75	LaNi _{4.25} Al. 75	annealed & sensitized	annealed	372	13383
7	2	Vertical	40	LaNi _{4.25} Al. 75	LaNi _{4.25} Al. 75	cleaned & thinned	cleaned	368	13241

TABLE 3. Exposure conditions for cycling system samples.

FIGURE 1. Scanning electron micrograph (SEM) of interior surface of 21 Month Bed container. Used in tritium service for 21 months. Intergranular surface ditches clearly observable.

FIGURE 2. Photograph of machined compatibility sample and quartz encapsulated machined compatibility sample. Sample 1/2 inch square.

FIGURE 3. Diagram of cycling systems. Horizontal (top) and vertical (bottom) orientation referred to in Table 2.

FIGURE 4. Diagram of electrical and cooling air connections to each cycling system. Case shown where front resistance heated, rear air cooled. Variable transformers adjust power dissipated in heaters. Timed relay automatically switches side being heated or cooled.

FIGURE 5. Variation of temperature of each tube and total system pressure with time of cycling system during cycling (typical). Systems monitored periodically to ensure proper operation over extended exposure time.

FIGURE 6. SEM of unexposed (top) and one year exposed (bottom) Type 304 stainless steel tubes used in cycling experiments- used as received. (Experiment 7, rear tube in Table 3).

FIGURE 7. SEM of interior surface of unexposed (top) and exposed (bottom) Type 316 stainless steel gas sample bottles used in palladium-coated kieselguhr cycling experiments (*Table 1.*). Note pronounced intergranular ditching in both unexposed and exposed bottles. (Sample bottle manufactured by Whitey.)

FIGURE 8. SEM of unexposed (top) and exposed (bottom) Type 304 stainless steel tubes used in cycling experiments. Both annealed at 1050°C for 5 minutes (before exposure). (Experiment 6, rear tube in Table 3).

FIGURE 9. SEM of unexposed (top) and exposed (bottom) machined compatibility sample. Exposed to 1500 psia hydrogen and $\text{LaNi}_{4.7}\text{Al}_{0.3}$ at 300°C. for 1 week (*Table 1*). No evidence of reaction.

FIGURE 10. SEM of exposed tube in cycling Experiment 1- exposed 686 days (front tube *Table 3*). Note implanted $\text{LaNi}_{4.7}\text{Al}_{0.3}$ powder in wall: no reaction evident. (See Fig. 6 for unexposed microstructure.)

FIGURE 11. SEM of base (top) and weld metal (bottom) of interior surface of 21 Month Bed. Intergranular ditching similar on both surfaces, indicating acid cleaning after weld fabricated.

FIGURE 12. Photograph of unexposed and exposed machined compatibility sample. Note lack of oxidation on parts of exposed sample in contact with $\text{LaNi}_{4.7}\text{Al}_{0.3}$ powder.

**DATE
FILMED**

7 / 30 / 93

END