MACTED

COAL DESULFURIZATION

BY A

MICROWAVE PROCESS

BY

P.D. ZAVITSANOS, J.A. GOLDEN, AND K.W. BLEILER

TECHNICAL PROGRESS REPORT

FEBRUARY 1981 - MAY 1981

WORK PERFORMED UNDER CONTRACT NO. DE-AC22-80PC30142

GENERAL ELECTRIC COMPANY
RESEARCH AND ENGINEERING DEPARTMENT
RE-ENTRY SYSTEMS DIVISION
PHILADELPHIA, PA 19101

DISCLAIMER
This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

EXPERIMENTAL RESULTS

Desulfurization experiments were carried out using the 6 KW, 2450 MHz Flow Reactor System described in the March 1981 Progress Report. The program has been directed toward the combination of physical separation and microwave exposure with NaOH to increase sulfur removal. The following treatment sequence has been used with good results:

- Step 1. Expose 1/4-1" raw coal to microwaves.
- Step 2. Crush the treated coal and separate the sample into float/sink fractions.
- Step 3. Add NaOH to the float fraction and re-expose the sample to microwaves.
- Step 4. Wash, add NaOH and expose to microwaves.

This procedure has produced up to 89% sulfur removal and as low as .31 #S/10⁶ BTU. Ash analyses on these samples showed as high as 40% reduction. The calorific value was increased in almost all samples.

The geographic origin of the coals used in these experiments is listed below:

<u>PSOC #</u>	
345	Lower Kittanning Seam, PA
255	Lower Kittanning Seam, PA
270	American Seam, Quinton, AL
272	Kentucky #9 Seam, KY

Table 1 summarizes data on sulfur, ash and calorific values. Sulfur forms* analyses were performed on a number of the runs listed in Table 1. These data are shown in Table 2.

* The sulfur forms analysis was performed by Smith, Rudy & Company, Analytical Chemists, Phila., PA.

TABLE 1. SUMMARY OF SULFUR, ASH AND CALORIFIC VALUE ANALYSES
6 KW, 2.45 GHz FLOW REACTOR EXPERIMENTS

PSOC #	RUN #	TOTAL SULFUR WT %					CALORIFIC VALUE	#S/10 ⁶	% ASH	% S LOSS
		Raw Coal	Microwave	Float/ Sink Crush	Float	NaOH + MW	Btu/# Dry	Btu		
255 (LOWER KITTANNING SEAM, PA)	383*	2.45	RAW COAL				12385	1.93	19.4	
	379		1.89		1.17					
	380					.73 ⁺	14226	0.43	5.13	70.2
	414* (DT RUN 380)					.27 ⁺				89.0
	399*	2.12	RAW COAL				12253	1.73	20.37	
	400		1.75		1.06					
	405*					.70 ⁺	13092	0.53	11.89	67.0
	418* (DT RUN 405)					.46 ⁺				78.3
	402		1.81		1.16					
	406					.70 ⁺				67.0
270 (AMERICAN SEAM, ALA)	398*	2.66	RAW COAL				12234	2.17	18.80	
	397		1.58		1.50					
	401*					.72 ⁺	13351	0.59	7.48	72.9
	417* (DT RUN 401)					.44 ⁺	13998	0.314		83.5
	420	1.39	RAW COAL							
	419		1.38		1.40					
	421					1.10 ⁺				20.9

* SULFUR FORMS ARE GIVEN IN TABLE 2.

+ HCL WASH BEFORE SULFUR ANALYSIS

DT = REPEAT ALKALI + MW EXPOSURE

(CONT'D)

TABLE 1. SUMMARY OF SULFUR, ASH AND CALORIFIC VALUE ANALYSES
6 KW, 2.45 GHz FLOW REACTOR EXPERIMENTS

PSOC #	RUN #	TOTAL SULFUR WT %					CALORIFIC VALUE	#S/10 ⁶	% ASH	% S LOSS
		Raw Coal	Microwave	Float/ Sink Crush	Float	NaOH + MW	Btu/# Dry	Btu		
(LOWER KITTANNING SEAM, PA)	382*	3.14	RAW COAL				14050	2.23	7.3	
	381		2.24							
	410 (DT 381)		1.16							63.1
	386*	4.26	RAW COAL				13957	3.05	8.82	
	385		3.26							
	389					1.62 ⁺ 1.82	13935	1.16	5.73	62.0
	415* (DT 389)					.59 ⁺	13300	0.444		86.2
	392*	2.03	RAW COAL				13840	1.47	8.20	
	391		2.68		1.75					
	393					1.17 ⁺	14634	0.80	3.50	42.4
	416* (DT 393)					.51 ⁺	13663	0.373		74.9
	403	3.04	RAW COAL							
	404		2.84		1.86					
	407					1.36 ⁺				55.3
	382	3.14	RAW COAL							
	384					1.34				
	409* (DT 384)					.50 ⁺				

(CONT'D)

TABLE 1. SUMMARY OF SULFUR, ASH AND CALORIFIC VALUE ANALYSES
6 KW, 2.45 GHz FLOW REACTOR EXPERIMENTS

<u>PSOC #</u>	<u>RUN #</u>	<u>TOTAL SULFUR WT %</u>					<u>CALORIFIC</u> <u>VALUE</u>	<u>#S/10⁶</u>	<u>% ASH</u>	<u>% S LOSS</u>
		<u>Raw</u> <u>Coal</u>	<u>Microwave</u>	<u>Float/</u> <u>Sink</u> <u>Crush</u>	<u>Float</u>	<u>NaOH</u> <u>+ MW</u>	<u>Btu/# Dry</u>			
272 (KENTUCKY #9)	412	4.05* RAW COAL								
	411		2.84		2.65					
	413					2.21 ⁺				45.4

TABLE 2. SULFUR FORMS ANALYSES ON RAW AND MICROWAVE TREATED COAL SAMPLES

SMITH, RUDY & COMPANY

ANALYTICAL

CHEMISTS

20 NORTH THIRD STREET

PHILADELPHIA, PA. 19106

May 13, 1981

General Electric Company
R.E.S.D.
Philadelphia, Pa.

P.O.#P 65939

ANALYSIS OF COAL (Raw Samples)

<u>Sample Identification</u>	<u>Moisture</u>	<u>Tot.Sul.</u>	<u>Pyritic Sul.</u>	<u>Organic Sul.</u>	<u>Sulfate Sul.</u>
Run #382	1.51	2.93	1.54	1.19	.20
Raw Coal PSOC 345	Dry	2.97	1.56	1.21	.20
3/8-1"					
Run #383	1.06	2.33	1.19	.86	.28
Raw Coal PSOC 255	Dry	2.35	1.20	.87	.28
1/4-3/8"					
Run #386 3/13/81	1.79	4.16	2.69	1.10	.37
Raw Coal #345	Dry	4.24	2.74	1.12	.38
1/4-1/2"					
Run #392 3/27/81	1.51	1.99	.89	.99	.11
Raw Coal #345 Coal	Dry	2.02	.90	1.01	.11
30-200 m					
Run #398 4/1/81	1.30	2.55	1.29	.92	.34
PSOC 270 Coal	Dry	2.58	1.31	.93	.34
Raw Coal 3/8-1"					
Run #399 4/1/81	.83	1.91	1.03	.88	.00
PSOC 255	Dry	1.93	1.04	.89	.00
Raw Coal 3/8-1"					

SMITH, RUDY & COMPANY

By

(CONT'D)

TABLE 2. SULFUR FORMS ANALYSES ON RAW AND MICROWAVE TREATED COAL SAMPLES

SMITH, RUDY & COMPANY

ANALYTICAL

CHEMISTS

20 NORTH THIRD STREET

PHILADELPHIA, PA. 19106

May 13, 1981

General Electric Company
R.E.S.D.
Philadelphia, Pa.

P.O.#P 65939

ANALYSIS OF COAL (Treated Samples)

<u>Sample Identification</u>	<u>Moisture</u>	<u>Tot. Sul.</u>	<u>Pyritic Sul.</u>	<u>Organic Sul.</u>	<u>Sulfate Sul.</u>
Run #414 4/16/81	9.51	.24	.00	.22	.02
#255 Coal + NaOH Treated	Dry	.27	.00	.25	.02
Rerun of #380 HCL Wash					
Run #415 4/16/81	11.40	.51	.00	.47	.04
345 Coal + NaOH	Dry	.58	.00	.53	.05
Rerun of 389 HCL Wash					
Run #416	As Rec'd	.43	.00	.43	.00
#345 Coal + NaOH Treated					
Rerun of 393 HCL Wash					
Run #417 4/17/81	7.98	.42	.00	.00	.00
#270 Coal + NaOH Treated	Dry	.46	.00	.00	.00
Rerun of Run 401 HCL Wash					
Run #418 4/17/81	5.13	.40	.00	.40	.00
#255 Coal + NaOH Treated	Dry	.42	.00	.42	.00
Rerun of Run 405					
Run #401 4/15/81	As Rec'd	.61			
Run #405 4/15/81	As Rec'd	.52			
Run #409	As Rec'd	.51			
Rerun of 384					

SMITH, RUDY & COMPANY

By *[Signature]*

Detailed sulfur reduction histories accomplished by the various steps are shown in Figures 1 through 4.

In previous work, NaOH was added to the coal sample from a water solution and then vacuum dried to 20-30% water level to optimize coupling to the microwave field. This method worked quite well but was time consuming. A new technique is now being used. The coal sample is mixed with NaOH powder, then water is added (~ 25 wt % H_2O) to the powdered mix. The sample is now ready for exposure to microwaves.

FIGURE 1. SULFUR REDUCTION HISTORY FOR PSOC-255

70X100 1/10 Inch Divisions

GENERAL ELECTRIC COMPANY, SCHENECTADY, N. Y., U.S.A.

FN-521-A (8-50)

FIGURE 2. SULFUR REDUCTION HISTORY FOR PSOC-345

70X100 1/10 Inch Divisions

GENERAL ELECTRIC COMPANY, SCHENECTADY, N. Y., U.S.A.

PN-521-A (8-50)

FIGURE 3. SULFUR REDUCTION HISTORY FOR PSOC-270

70X100 1/10 Inch Divisions

GENERAL ELECTRIC COMPANY, SCHENECTADY, N. Y., U.S.A.

FN-521-A (8-50)

FIGURE 4. SULFUR REDUCTION HISTORY FOR PSOC-272