DOE/MC/27286--3179

**THE DEVELOPMENT OF AN INTEGRATED MULTISTAGE
FLUID BED RETORTING PROCESS**

DE93 006658

Technical Report for the Period

April 1, 1992 - June 30, 1992

S.D. Carter
D.N. Taulbee
T.L. Robl
J.C. Hower

August 1992

Work Performed Under
Cooperative Agreement No:
DE-FC21-90MC27286

For

U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center

By

University of Kentucky
Center for Applied Energy Research
Lexington, Kentucky

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

This report summarizes the progress made on the development of an integrated multistage fluidized bed retorting process (KENTORT II) during the period of April 1, 1992 through June 30, 1992 under Cooperative Agreement No. DE-FC21-90MC27286 with the Morgantown Energy Technology Center, U.S. Department of Energy. The KENTORT II process includes integral fluidized bed zones for pyrolysis, gasification, and combustion of the oil shale. The purpose of this program is to design and test the KENTORT II process at the 50-lb/hr scale.

The raw oil shale sample for the program was mined, prepared, characterized and stored this quarter. The shale that was chosen was from the high-grade zone of the Devonian Cleveland Member of the Ohio Shale in Montgomery County, Kentucky. The shale was mined and then transported to the contractor's crushing facility where it was crushed, double-screened, and loaded into 85 55-gal barrels. The barrels, containing a total of 25-30 tons of shale, were transported to the CAER where the shale was double-screened, analyzed and stored.

A major objective of the program is the study of solid-induced secondary coking and cracking reactions. A valved fluidized bed reactor has been the primary apparatus used for this study prior to this quarter, but two additional techniques have been initiated this quarter for the study of other aspects of this issue. First, the two-stage hydrolysis reactor at the University of Strathclyde, Glasgow, Scotland, was used to study the coking tendency of shale oil vapors under a wide range of pyrolysis and hydrolysis conditions. This work enabled us to examine secondary reactions under high pressure conditions (up to 150 bar) which were previously unavailable. Second, the development of a fixed bed reactor system was initiated at the CAER to study the coking and cracking characteristics of model compounds. A fixed bed apparatus was necessary because the conversion of model compounds was too low in the fluidized bed apparatus.

ACKNOWLEDGMENT

The work described herein was performed at the University of Kentucky Center for Applied Energy Research under Cooperative Agreement DE-FC21-90MC27286 with the Laramie Project Office of the Morgantown Energy Technology Center (METC), U.S. Department of Energy.

TABLE OF CONTENTS

LIST OF FIGURES	v
LIST OF TABLES	v
INTRODUCTION AND BACKGROUND	1
OBJECTIVES	2
MINING OF OIL SHALE SAMPLE	3
SECONDARY CRACKING AND COKING OF SHALE OIL VAPORS	5
Secondary Reactions in a Two-Stage Hydrolysis Reactor	5
Apparatus and Procedure	5
Materials	7
Results and Discussion	7
Summary	10
Hydrocarbon Cracking Study	11
Introduction	11
Approach	11
REFERENCES	14

LIST OF FIGURES

Figure 1.	Cumulative size distribution of KENTORT II run of mine feedstock. . .	3
Figure 2.	Schematic diagram of the two-stage fixed-bed hydrolysis reactor. . .	6
Figure 3.	Schematic of model compound cracking reactor	12

LIST OF TABLES

Table 1.	KENTORT II feedstock, run of mine, air-dried. Elemental data is in weight percent (as-received basis).	4
Table 2.	Ultimate Analyses (As-Received Basis) of the Raw and Combusted Cleveland Oil Shale (wt%).	7
Table 3.	Run Conditions and Selected Results from the Two-Stage Hydrolysis Reactor.	8

INTRODUCTION AND BACKGROUND

It is now well accepted that fluidized bed pyrolysis of oil shale at near-zero hydrogen partial pressure will generate higher than Fischer assay oil yields. This enhancement varies according to shale type, but for most shales of the world it can be significant, and the oil shales contained in the U.S. are not exceptions. It has been shown that fluidized bed pyrolysis of eastern and western U.S. oil shales can enhance oil yields by 50%^{1, 2, 3, 4, 5} and 10%^{6, 7} above Fischer assay, respectively. In addition, fluidized bed technology offers the advantages of rapid pyrolysis kinetics (short solid residence time), total use of mined shale, and thermal efficiency. The Center for Applied Energy Research (CAER) has developed a commercial retorting concept, KENTORT II, which is based on fluidized bed technology. This process has been successfully demonstrated in a 3-inch diameter, 5-lb/hr system at the CAER using eastern U.S. oil shale.⁸ The objective of the current program is to scale the KENTORT II process to a 6-inch diameter, 50-lb/hr reactor.

Approximately 40% of the original carbon remains in the spent shale following fluidized bed pyrolysis of Eastern shale. This is more carbon than is required to provide process heat, and an intermediate gasification stage was included in the KENTORT II design to utilize this excess carbon for synthesis gas production. The gasification section is also important because it permits steam/iron sulfide reactions to go nearly to completion. These reactions remove the majority of the sulfur from the shale in the case of eastern shale because approximately 90% of its sulfur is present as iron sulfides. The removal of sulfur from the shale as H_2S prior to combustion creates a relatively concentrated stream of H_2S which is easier to scrub than a dilute stream of SO_2 from combustion. The H_2S serves as feedstock for elemental sulfur production which improves process economics because of the by-product credit. For shales which do not contain large amounts of residual carbon and/or iron sulfides following pyrolysis, the gasification step is not plausible.

Following gasification, the remaining carbon in the shale is combusted to provide process heat. The heat of combustion is transferred to the gasification and pyrolysis zones via recirculation of the processed shale because sufficient heat cannot be transferred using gases alone. Following combustion, essentially all of the carbon and sulfur in the shale have been removed. This has important environmental implications because the potential for acid drainage by the disposed spent shale is significantly reduced when the sulfur content is low.^{9, 10}

Operation of the KENTORT II process was shown to be viable at the 5-lb/hr scale during the previous cooperative agreement, but because of the small size of the unit, questions relative to scale-up remain. One issue is the effect that scale-up will have on the coking and cracking losses in the pyrolysis reactor. Efforts were continued this quarter to more fully understand these phenomena so that a suitable experimental matrix and optimized run conditions may be chosen for the 50-lb/hr retort.

OBJECTIVES

The primary objective of this program is to perform the research necessary to design, construct and test the KENTORT II process at the 50-lb/hr scale. The tasks for the program are listed below:

Task 1 - Design and Construction of the KENTORT II Prototype Unit

- 1.1 - Cold-Flow Modeling of the Reactor
- 1.2 - Mini-Plant Investigation of Solids Recycle (Cracking and Coking Kinetics)
- 1.3 - Final Design and Construction of the KENTORT II Prototype Unit

Task 2 - Operation of the Prototype Unit

- 2.1 - Reactor and System Shakedown
- 2.2 - Prototype Operational Runs

Task 3 - Shale Acquisition and Product/By-Product Characterization

- 3.1 - Collection and Characterization of the Oil Shale Feedstock
- 3.2 - Characterization of the KENTORT II Materials and Products for Utilization and Environmental Characteristics
 - 3.2.1- Characterization of KENTORT II Products for Asphalt Application
 - 3.2.2- Characterization of Nitrogen and Mineralogic Transformations in the KENTORT II Process
- 3.3 - Economic Evaluations

Efforts were directed toward subtasks 1.2 and 1.3 during this reporting period. The objective of subtask 1.2 is to gain a better understanding of the kinetics of cracking and coking of shale oil vapor over recycled shale in the KENTORT II process. With this knowledge, the design and operation of the solid-recycle loop to the pyrolyzer may be adjusted to minimize oil losses. With the results from subtasks 1.1 and 1.2 available, it is the objective of subtask 1.3 is to complete the design of the 50-lb/hr retort. The mining and initial characterization of the raw oil shale sample for the project was initiated this quarter and represents subtask 3.1.

MINING OF OIL SHALE SAMPLE

Oil shale from the Cleveland Member of the Ohio Shale was selected for use in the KENTORT II study based upon the judgment that it represented one of the shale types in the eastern U.S. that has the highest probability for initial commercial development. Mining of the shale was conducted in Montgomery County, Kentucky, during this quarter. The contractor cleared the hillside and, in the course of site preparation, removed about 5 tons of the Mississippian Sunbury Shale and 5 tons of the Cleveland Shale, placed the shale in bags, and transported the bags to the CAER. Site preparation continued with the development of a 30 x 30 foot bench on the top of the Cleveland. Thirty-two eight-foot holes on approximately four-foot centers were drilled, loaded, and detonated. An estimated 100 tons of shale was loosened by the blast. The shale was excavated and transported to the contractor's crushing facility where it was crushed, double-screened, and loaded into 85 55-gal barrels. The barrels, containing a total of 25-30 tons of shale, were then transported to the CAER.

The sample was reduced in size using a crushing train at a limestone quarry, and a small amount of contamination was present, as expected. The limestone pieces were large and will be easily screened out. The sample was mined and prepared during a period of extremely wet weather, so it will have to be dried before further processing.

The target size range for the samples was 8 x 0 mesh, with as much near 8 mesh materials as possible. The particle size distribution of an air-dried aliquot was classified by screening (Figure 1, Table 1). In general, the shale was found to be close to the targeted size distribution. There was, however, a significant percentage of oversize material which was in the 4 x 8 mesh (~2.4 x 4.8 mm) size range. This is likely due to differences in the crushing behavior of the shale compared to the limestone.

One particular concern in preparing the sample was excessive fines generation, especially in the very fine size range (i.e. -60 mesh or -0.25 mm). This component of the shale was only 11% of the total, which, based upon previous research, is well within acceptable limits.¹¹

Each size fraction was analyzed for total carbon, hydrogen and nitrogen which averaged 11.7%, 1.2% and 0.8%, respectively. This compares very well with the total carbon for the defined resource zone from Montgomery County where cores D-5 and D-6 averaged 11.5% and 12.0%, respectively.¹² There may be a slight trend toward lower

Figure 1. Cumulative size distribution of KENTORT II run of mine feedstock.

Table 1. KENTORT II feedstock, run of mine, air-dried. Elemental data is in weight percent (as-received basis).

	Size in mm		Weight%	C	H	N	S	Ash
	Plus	Minus						
+1/4	6.35							
1/4x4	4.75	6.35	3.0%	12.6	1.4	0.8	2.0	80.9
4x8	2.36	4.75	37.3%	11.7	1.2	0.8	2.0	81.7
8x12	1.70	2.36	14.0%	11.5	1.2	0.8	2.1	81.7
12x16	1.18	1.70	11.3%	11.8	1.2	0.8	2.0	81.8
16x18	1.00	1.18	5.5%	11.8	1.2	0.8	2.1	80.6
18x20	0.85	1.00	2.3%	11.7	1.2	0.7	2.1	81.0
20x30	0.60	0.85	5.5%	11.4	1.1	0.7	1.6	82.6
30x60	0.25	0.60	9.9%	11.3	1.1	0.8	1.8	82.8
60x100	0.15	0.25	3.1%	11.3	1.1	0.8	1.8	82.1
-100		0.15	8.0%	11.3	1.3	0.7	1.8	81.8

carbon values with decreasing size (Table 1). However, the standard deviation for the carbon was 0.4 or approximately 3% of the mean. This is comparable to an analytic uncertainty of approximately 2% for this determination. Thus any variation in carbon with particle size may not be of significance.

Sample preparation plans for the next quarter will include air drying the sample and screening out the +8 mesh and -60 mesh material. The fine fraction will be stored separately. It will be used for blending with the 8x60 mesh materials (2.4 x 0.25 mm). This approach will allow fines content of the feedstock to be treated as a variable in the experimental design of the runs.

SECONDARY CRACKING AND COKING OF SHALE OIL VAPORS

The objective of this task is to further our understanding of the chemistry and kinetics associated with solids-recycle retorting. A valved fluidized bed reactor has been the primary apparatus used for this study prior to this quarter, but two additional techniques have recently been initiated this quarter for the study of other aspects of this issue. First, the two-stage hydropyrolysis reactor at the University of Strathclyde, Glasgow, Scotland, was used to study the coking tendency of shale oil vapors under a wide range of pyrolysis and hydropyrolysis conditions. This work enabled us to examine secondary reactions under high pressure conditions (up to 150 bar) which were previously unavailable. Second, the development of a fixed bed reactor system was initiated at the CAER to study the coking and cracking characteristics of model compounds. A fixed bed apparatus was necessary because the conversion of model compounds was too low in the fluidized bed apparatus.

Secondary Reactions in a Two-Stage Hydropyrolysis Reactor

Apparatus and Procedure. The reactor consisted of high-pressure tubing (0.79 cm I.D.) which was configured for both one- and two-stage operation (see Figure 2). The first stage consisted of a bed of raw oil shale supported by a wire wool plug. By establishing a low-voltage potential across the first stage using a high-ampere transformer, the shale was heated to pyrolysis temperature. This method of heating provided a uniform temperature within the bed of shale and enabled high heating rates to be achieved (up to 5°C s^{-1}). When a second stage was utilized, it was heated by a furnace which enclosed the reactor tube. The second stage was preheated to its target temperature prior to the heating of the first stage. Sweep gas (N_2 or H_2) flowed downward and carried the reaction products to a dry-ice-cooled coil where liquids were condensed and collected.

In all tests, the bed of raw oil shale (first stage) was heated at 5°C s^{-1} to a soak temperature of 520°C and held there for 10 minutes. Sweep gas (N_2 or H_2) constantly flowed through the reactor during the heat-up and soak periods. The gas flowrate was measured downstream of the pressure let down valve, and a representative sample was collected for analysis of $\text{C}_1\text{-C}_4$ by gas chromatography. Following each run, the cold trap was weighed and rinsed with toluene to recover the liquids. Dean-Stark analysis was performed on the toluene wash to determine moisture content and the oil content by-difference. Other tests done on the oils include size exclusion chromatography and ^1H -NMR. In some cases a neat oil product was recovered so that certain tests (i.e. elemental analysis) would be facilitated. It should be noted, however, that this was not possible in all cases because of the small amount of liquids produced. The weight loss of the reactor was recorded following each run, and the pyrolysis char and second stage material (if present) were recovered for ultimate analysis.

Figure 2. Schematic diagram of the two-stage fixed-bed hydropyrolysis reactor.

A series of single-stage tests was performed to provide baseline data for the two-stage runs. Approximately 15 g of raw oil shale was loaded into the reactor for the single-stage tests which resulted in a fixed-bed height of 28 cm. The bed of shale was situated near the outlet of the heated zone (61-cm length) to reduce secondary reactions. Single-stage tests included nitrogen sweep at 1 and 50 bar pressure and hydrogen at 50 bar. For these runs, the superficial gas velocity ranged from 0.2 to 2 m/s because of the large differences in total pressure and the limits of the gas metering system.

For two-stage tests a smaller charge of raw shale (10 g, 19 cm depth) was used because of space limitations within the reactor for the first stage (33-cm heated length). Approximately 5 g of substrate made up the second stage which resulted in bed heights of 13 cm and 15 cm for the combusted shale and hydrotreating catalyst, respectively. The heated length of the second zone was 46 cm and was maintained at 520°C and 400°C for the combusted shale and catalyst, respectively. Two-stage tests included nitrogen sweep at 1 and 150 bar and hydrogen sweep at 50, 100, and 150 bar for each substrate. In addition, a "single-stage" run was performed in the two-stage configuration because no comparable run at 150 bar H₂ pressure was performed in the single-stage setup.

Materials. The master sample of oil shale utilized in these studies was from the Cleveland Member of the Ohio Shale from northeastern Kentucky, USA (see raw shale analysis in Table 2). The shale was prepared to a size distribution of $-250\mu\text{m} +150\mu\text{m}$. This shale sample was used both for the production of shale oil vapors in the first stage and as the starting material for the generation of the combusted shale which was used in the second stage. The combusted shale was generated in air at 973K in a 7.6-cm diameter fluidized bed reactor. A commercially available Ni/Mo γ -alumina catalyst was precalcined at 400°C for 12 hours prior to use as a second stage material.

Table 2. Ultimate Analyses (As-Received Basis) of the Raw and Combusted Cleveland Oil Shale (wt%).

	C	H	N	S	Ash
Raw Shale	16.0	1.9	0.8	1.9	74.1
Combusted Shale	1.4	0.2	0.6	0.2	97.0

Results and Discussion. Since product analyses were not complete at this writing, a comprehensive presentation of the results and conclusions of the study will not be attempted here. Instead, the discussion will primarily focus on total hydrocarbon evolution from the first stage and subsequent coke deposition in the second stage. Information on substrate-catalyzed cracking reactions will be summarized later when all results are available for interpretation.

Mass transfer limitations were small for these experiments because of the rapid particle heat-up and the sweep gas through the bed, so carbon conversion to volatile products was higher than Fischer assay for the nitrogen-swept runs at 1 bar total pressure (see Table 3). Utilization of 50-bar N_2 sweep gas resulted in slightly lower carbon conversion. As anticipated, 50-bar H_2 pressure increased significantly the conversion to volatile products (approx. 73%) at 10 minutes solid residence time. These results are slightly lower than those reported by IGT who generally utilizes 30 minutes solid residence time.¹³ The increased conversion at the longer residence times is most likely attributable to extra hydrocarbon gas production. It is emphasized, however, that the purpose of this study was not the study of hydropyrolysis, *per se*, but it was the study of secondary reactions, and by nature of the apparatus, hydropyrolysis was a necessary element of the investigation.

Carbon deposition onto the combusted shale in 1 bar nitrogen accounted for 4% of the carbon in the raw shale. Under otherwise similar conditions, carbon deposition on the combusted shale was slightly lower at a pressure of 150 bar, but when considering

Table 3. Run Conditions and Selected Results from the Two-Stage Hydropyrolysis Reactor.

Run	Sweep Gas	2nd Stage Substrate	Press., Bar	No. of Stages	Gas Vel., m/s	2nd Stage Temp., K	1st Stage C Conv.(%)	Alkene/Alkane Ratios		
								C2	C3	C4
2	N2		1	1	0.99		50.22	na	na	na
3	N2		1	1	1.98		53.35	na	na	na
7	N2		1	1	1.98		51.73	0.489	1.015	0.882
4	N2		53	1	0.19		49.10	na	na	na
5	H2		51	1	0.19		71.75	na	na	na
6	H2		51	1	0.19		73.41	0.326	0.701	0.702
18	H2	none	150	2	0.07	793	75.58	0.354	0.612	0.000
14	N2	NiMo	1	2	2.47	793	51.73	0.524	1.141	0.992
10	N2	Comb Shale	1	2	2.47	793	49.50	0.518	1.134	0.995
19	N2	Comb Shale	150	2	0.07	793	47.51	0.382	0.944	nd
9	H2	Comb Shale	49	2	0.30	793	73.18	0.441	0.748	nd
17	H2	Comb Shale	150	2	0.07	793	81.12	0.209	0.475	nd
12	H2	NiMo	48	2	0.31	673	69.32	0.112	0.278	nd
13	H2	NiMo	100	2	0.15	673	80.97	0.064	0.205	nd
15	H2	NiMo	150	2	0.07	673	79.75	0.000	0.000	0.000

Run	Sweep Gas	2nd Stage Substrate	Press., Bar	Carbon Distribution (wt% C/wt% C in r.s.)			C Balance (%)
				Char	2nd Stage	Oil	
2	N2		1	0.498		0.195	69.31
3	N2		1	0.467		0.412	87.83
7	N2		1	0.483		0.389	92.15
4	N2		53	0.509		0.322	83.11
5	H2		51	0.283		0.685	96.75
6	H2		51	0.266		0.677	110.23
18	H2	none	150	0.244	na	0.608	92.87
14	N2	NiMo	1	0.483	0.168	0.273	97.17
10	N2	Comb Shale	1	0.505	0.038	0.266	85.83
19	N2	Comb Shale	150	0.525	0.023	0.157	76.27
9	H2	Comb Shale	49	0.268	0.007	0.509	92.81
17	H2	Comb Shale	150	0.189	0.000	0.669	89.23
12	H2	NiMo	48	0.307	0.117	0.465	99.75
13	H2	NiMo	100	0.190	0.143	0.546	103.36
15	H2	NiMo	150	0.202	0.150	0.509	91.65

standard analytical error, the amounts of carbon can be considered essentially equal. Nevertheless, a zeroth-order reaction rate mechanism in terms of oil vapor partial pressure for char formation is indicated under these conditions. When the Ni/Mo catalyst was used as the 2nd-stage substrate, nearly 17% of the carbon originally present

in the raw shale was deposited onto the catalyst. This is consistent with the hypothesis that carbon deposition is controlled by the available surface area of the substrate since the catalyst has a total BET surface area of 180 m²/g compared to 20 m²/g for the combusted shale.

Hydrogen partial pressures of 50 and 150 bar effectively reduced carbon deposition onto the combusted shale to near zero. Under otherwise equivalent conditions, however, substantial carbon deposition occurred on the catalyst, even at 150 bar H₂ partial pressure. This result appears to indicate that high rates of coke formation may occur when crude shale oils from high-yield processes are catalytically upgraded. This is an area which deserves much more attention since coke formation during upgrading is equivalent to the loss of oil yield during the pyrolysis process itself.

The determination of oil yield was probably the most uncertain measurement from this set of experiments, as it is for almost all pyrolysis procedures. Oil trapping inefficiency and the measurement of the amount of water co-collected with the oil mainly contributed to the uncertainty in oil yield determinations. Eastern oil shales form an aerosol, especially when sweep gas is used, that is particularly difficult to trap, and the dry-ice-cooled trap was not sufficient to completely collect the oil in this study. Light oil and water were present in the glass wool in the outlet of the trap following each run which suggests that some liquids were escaping. In most cases the water content of the toluene wash from the trap was too low to be detected by the Dean-Stark method, so it was assumed that the raw shale produced 4 wt% water which was collected in the trap. Inferences from relatively small changes in oil yield should, therefore, be considered carefully.

Oil yields generally followed the trends suggested from the carbon contents of the first and second-stage solids. The highest oil yields were obtained under high H₂ partial pressure and no second-stage substrate. Combusted shale in the second stage did not seriously affect oil yield, as opposed to the upgrading catalyst, which significantly lowered the measured oil yield. The lowest oil yields were obtained in N₂-swept runs when catalyst was present in the second stage or the total pressure was high.

As anticipated, the hydrogenation of the primary pyrolysis products increased at higher H₂ partial pressures when the upgrading catalyst was utilized in the second stage. This was clearly demonstrated by the alkene/alkane ratios of light gases (C₂-C₄) which decreased with increasing H₂ partial pressure until disappearing to zero at 150 bar. Hydrogenation was visually apparent for the oil which had passed through the catalyst at 150-bar H₂ partial pressure; it was light in color, was nearly transparent, and did not change in appearance with time. Oils produced from tests without the upgrading catalyst became more aromatic (as determined by ¹H NMR) at either increased H₂ partial pressure or exposure to combusted shale.

The gas yields were erratic, especially between high- and low-pressure runs, and this appears to be due to a systematic sampling error. The apparatus was designed for high-pressure operation, so a relatively large sweep-gas flowrate, measured at ambient conditions, is required for a fast velocity within the reactor. At atmospheric pressure, however, a much lower gas flowrate is required, and much less gas is collected for analysis. Because of the small volume of gas, it was not sufficient to displace air contamination in the relatively large gas sampling system, and the samples from the low-pressure runs probably became diluted with room air. Unfortunately, confirmation of this was not available because only the analysis of hydrocarbon gases by GC was performed. While the absolute gas yields are questionable, the alkene/alkane ratios are still valid and provide useful indications of the relative extent of cracking, coking, and hydrogenation reactions.

Summary. This brief study has provided useful information that will complement the fluidized-bed coking kinetics study because of the ability to examine coking under high-pressure conditions. Since high pressures did not significantly enhance carbon deposition, it appears that the coke formation rate is largely influenced by the rate of the surface reaction.

Another important facet of this work was the study of the upgrading behavior of the shale oil vapors. The oils produced in the two-stage mode were significantly upgraded as displayed by the nearly clear liquid that was produced. Of course, the extent of upgrading needs to be quantitatively determined, but the results are, nevertheless, encouraging. Coke formation on the upgrading catalyst was relatively high, even at high H_2 partial pressure, so more work in this area is needed.

Hydrocarbon Cracking Study

Introduction. Before exiting the reactor, liquid products generated during oil shale pyrolysis in the KENTORT II reactor are exposed to hot pyrolyzed, gasified, and combusted shale surfaces. Such exposure catalyzes secondary cracking and coking reactions resulting in both hydrocarbon loss and a shift to a lower average molecular weight product. Since coking reactions have a detrimental effect on process economics (and must be understood in order to be suppressed via design considerations), coking reactions and kinetics have been the topic of a previous study.

Though not as immediately detrimental to plant economics, cracking reactions within the reactor are also of concern in any systematic attempt at process optimization. For simplicity, cracking reactions are defined as reactions in which a molecule is cleaved to produce two or more smaller components with little or no carbon deposition in the initial step. Cleavage reactions result in production of stable gases and lower molecular weight liquids as well as unstable free radical intermediates. These latter tend to rapidly interact with other HC's or radical intermediates to produce a suite of products including H_2 , olefins, cyclic alkenes, aromatics, and coke. Thus, cracking reactions have a profound effect on product quality and yield, both good (lower average molecular weight and viscosity) and bad (eventual coke production). By improving our understanding of the rates and mechanisms for these catalyzed reactions, it is hoped that the processing conditions, particularly management of the heat transfer solids, can be optimized to produce a superior product.

In an approach similar to that of the coking kinetics research reported in previous quarters, an apparatus is being constructed to facilitate the study of hydrocarbon cracking reactions. This effort will attempt to measure the rate and, time permitting, identify the cracking pathways and mechanisms as a function of substrate, hydrocarbon type, and temperature.

Approach. A simplified schematic of the apparatus is shown in Figure 3. Nitrogen gas is metered to two parallel carrier lines which are routed to a heated valve oven. One of the carrier lines (termed the balancing gas) serves to maintain a constant total flow through the system regardless of valve position. The other, (termed the hydrocarbon line) carries both the model compound and metered Ar (used as a tracer gas). The model compound is introduced to the HC line via a Waters Assoc. model 6000 liquid chromatography pump, typically at 0.1-0.2 mL/min, and is vaporized prior to mixing with the N_2 -Ar blend.

Both carrier lines are heat traced and routed to a 3" diameter furnace operating at a selected target temperature. The two carrier lines pass through either a bypass reactor or a substrate reactor before being combined and routed to the inlet of a VG model EGA 300MM quadrupole mass spectrometer (QMS). The bypass and substrate tube reactors are 9" X 3/8" OD stainless steel. The bypass bed will be packed with an

Figure 3. Schematic of model compound cracking reactor

inert material, i.e., Ottawa sand. The substrate bed will be packed for most tests with either pyrolyzed, gasified, or combusted shale to simulate the solid surfaces to which vapor phase hydrocarbons are exposed in an integrated KENTORT II reactor. In addition, limited cracking tests will be conducted using kaolinite and illite substrates for comparison to the previously reported coking studies.

For most tests, the QMS will be operated in the multiple ion monitoring (MIM) mode. This permits the measurement of up to 16 selected masses at approximate 1 second intervals. For these tests, the masses for Ar, N₂, and the molecular ion of the study hydrocarbon, among others, will be selected. In addition, a log histogram run will be made from 0 amu to the molecular mass for each substrate/model compound combination.

In the initial tests, the model compounds studied will include a series of n-alkanes, n-1-alkenes, a set of aromatics and alkylated aromatics as well as a cyclic aliphatic and a cyclic alkene. These compounds were selected since they are representative of the major

hydrocarbon components produced from Eastern shale oil in the KENTORT II process. Time permitting, similar tests will be conducted on selected heteroatom components.

The reactor beds will be operated between 300 and 650°C to study both adsorption and cracking. A typical cracking sequence will entail establishing thermal equilibrium in the reactor beds under inert gas flow, initiating model compound flow across the bypass bed, starting QMS data collection to establish a response baseline, actuating the switching valve so that the HC stream is routed through the substrate bed for a selected time interval, and returning the switching valve to the bypass position to re-establish baseline. The drop in response of the molecular ion during the substrate exposure segment is a direct indicator of product cracking. Exposed substrates will also be analyzed for carbon content to determine the amount of coking that accompanies the measured cracking.

In a second series of experiments, the reacted product will be collected for GC-MS analysis. This should help clarify whether the reaction mechanism and path varies as a function of substrate or exposure time, that is, does the initial reaction differ between substrates or within a given substrate before and after coke deposition.

REFERENCES

1. Rubel, A.M., M.J. Margolis, J.K. Haley, and B.H. Davis, *1983 Eastern Oil Shale Symposium Proceedings*, 1983, IMMR83/089, University of Kentucky, Lexington, Ky.
2. Margolis, M.J., *1981 Eastern Oil Shale Symposium Proceedings*, 1981, University of Kentucky, IMMR82/066, Lexington, KY.
3. Richardson, J.H., E.B. Huss, L.L. Ott, J.E. Clarkson, M.O. Bishop, L.J. Gregory, and C.J. Morris, Lawrence Livermore National Laboratory, UCID-19548, 1982.
4. Ahmed, M.M., D.W. Parker, and D.H. Archer, *1982 Eastern Oil Shale Symposium Proceedings*, 1982, University of Kentucky, IMMR82/075, Lexington, KY.
5. Rubel, A.M. and S.D. Carter, *Preprints Div. Pet. Chem.*, ACS, 1984, 29, 202-208 (1).
6. Wallman, P.H., Tamm, P.W., and Spars, B.G., *ACS Symp. Ser. 163*, 1981, 93.
7. Bissel E.R., Burnham, A.K., and Braun, R.L., *I and EC Proc. Des. Dev.*, 1985, 24, 381.
8. Carter, S.D., Rubel, A.M., Robl, T.L., and Taulbee, D.N., 'The Development of the KENTORT II Process for Eastern U.S. Oil Shale,' 1990, Final Report for work performed under Contract No.: DE-FC21-86LC11086, DOE/LC/11086-2860.
9. Carter, S.D. and D.N. Taulbee, *Fuel Processing Technology*, 1985, 11, 251-272.
10. Robl, T.L., K. Cisler, G. Thomas, and D.W. Koppenaal, *1985 Eastern Oil Shale Symposium Proceedings*, 1985, University of Kentucky, KCERL/85-147, Lexington, Ky.
11. Schonfeld, G.A., Eastern Oil Shale Crushing Tests. *Proc., 1982 Eastern Oil Shale Symp.*, Institute for Mining and Minerals Research, University of Kentucky, Lexington, KY pp. 353-360
12. Bland, A.E., Robl, T.L., Koppenaal, D.W., Geochemistry of the New Albany, Ohio and Sunbury Shales in East-Central Kentucky, *Proc. 1981 East. Oil Shales Symp.*, Institute for Mining and Minerals Research, University of Kentucky, Lexington, KY, pp. 183-194.
13. Roberts, M, Rue., D. and Lau, F., *Proc. 1990 Eastern Oil Shale Symposium*, Univ. of Kentucky, 1992.

END

**DATE
FILMED**

3 / 15 / 93