DEPARTMENT OF MATERIALS SCIENCE & ENGINEERING
LEHIGH UNIVERSITY
Whitaker Laboratory #5
Bethlehem, Pennsylvania 18015-3195
(215) 758-4220

DOE/ER/45256--T2

DE92 008724

FINAL TECHNICAL REPORT

SUBMITTED TO: U. S. Department of Energy
Office of Energy Research
Office of Basic Energy Sciences
Division of Material Sciences
Washington, D.C. 20545

ATTENTION: Dr. R. J. Gottschall
Dr. J. Routbort
Metallurgy and Ceramics Branch

SUBJECT: GRAIN BOUNDARY DIFFUSION IN ORIENTED Ni_3Al
BICRYSTALS CONTAINING BORON

For period September 1, ¹⁹⁸⁶ to August 31, 1990

DOE Grant No. DE-FG02-86ER45256

Lehigh Account 535071

Submitted by:

Y. T. Chou
Principal Investigator

December 20, 1990

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DESCRIPTION OF RESEARCH AND RESULTS

INTRODUCTION

The present research program entitled "Grain Boundary Diffusion in Oriented Ni_3Al Bicrystals Containing Boron" was granted to Lehigh University for a period of three years (September 1, 1986 to August 31, 1989). It was extended with no additional cost to August 31, 1990. Because of the technical difficulties, the passage of the program has been alleviated from the one originally proposed. The work on grain boundary diffusion in Ni_3Al was partially completed. On the other hand, a number of new properties have been explored. Some additional efforts have been made on diffusion in newly discovered oxide superconductors. Based on the findings, eight (8) papers have been published or accepted for publication in technical journals and proceedings. Five manuscripts are currently in preparation and will be published in the next year (see the attached list of reports and publications).

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

RESEARCH ACTIVITIES

(1) Grain Boundary Diffusion in Ni_3Al

We had a very difficult experience on diffusion work. Since the bicrystals of Ni_3Al were not available, we proceeded to measure the grain boundary diffusion in polycrystalline Ni_3Al containing boron and hafnium. In this case, a total of 117 couples ($\text{Ni}_3\text{Al}/\text{Ni}$) were annealed in the temperature range from 700° to 1200°C , but only 14 couples were suitable for the concentration analysis. Furthermore, of the 18 grain boundaries analyzed, the data of 11 boundaries failed to meet the Whipple's condition ($\beta \geq 10$). However, the remaining data were sufficient to yield an activation energy of 91.7 kcal/mol, which is greater than the activation energy of the volume diffusion (73.2 kcal/mol). This is unusual. The present study indicates that the grain boundary diffusion in Ni_3Al is a very complex phenomenon and remains to be explored. A report summarizing the study is in preparation (B5 in the list of reports).

(2) Boron Softening in Ni_3Al

During our investigation on the effect of boron on hardness of Ni_3Al , a new phenomenon of boron-induced softening has been observed. The results led to the following conclusions: (a) addition of a small quantity (ppm) of boron decreases both the grain boundary hardness and the hardness of grain interiors, (b) in substoichiometric polycrystalline alloys of 24 at. %Al, the maximum softening effect appears at the boron level of 0.23 at. % (500 wt. ppm), and (c) in Ni_3Al single crystals, addition of 0.25 at. % boron decreases the hardness values on {100}, {110}, and {111} crystallographic planes. the

softening effect was explained by a mechanism of cross-slip of screw dislocations. The findings were summarized in six papers (A2, A3, A4, A5, A8, and B3 in the list of reports).

(3) Recrystallization and Grain Growth in Ni₃Al

In view of the dominant effect of boron on ductility of Ni₃Al, an investigation of the boron effect on recrystallization and grain growth in Ni₃Al was undertaken over the temperature range from 800° to 1000°C. Two sets of alloys were used, Ni - 24 at. % Al without boron and the same alloy doped with 0.23 at. % boron. At 16.7% deformation, the recrystallization process was described by the Johnson-Mehl-Avrami-Kolmogorov (JMAK) equation, $F(t) = 1 - \exp(-kt^n)$. The k values were found higher for the boron-free alloy, while the n values were near unity for both alloys with and without boron. The activation energies of recrystallization were found to be 488 kJ/mol for the boron-doped alloy and 476 kJ/mol for the boron-free alloy. The work will be presented at the Sixth International Symposium (JIMIS-6) on Intermetallic Compounds to be held in Japan, June 17-20, 1991 (B1 in the list of reports).

(4) Cation Diffusion in Oxide Superconductors

One way to increase the value of the parameter β in the grain boundary diffusion analysis is to reduce the diffusion time. This would require a more precise technique, such as the advanced electron microscopy (AEM), for concentration measurements. With this in mind, we were engaged in a joint research with DuPont to evaluate the interdiffusion of cations in YBa₂Cu₃O_{7- δ} superconducting film on ceramic substrates. The AEM data concluded that more cations in the superconducting phase diffuse into the Al₂O₃ sustrate

than into MgO or ZrO₂ substrate. The results are summarized in two technical papers (A6 and A7 in the list of reports).

(5) Stress Field of Grain Boundary Dislocations

Grain boundary dislocation is an important type of defects in grain boundary phenomena. However, explicit expressions for the stress field of a grain boundary dislocation have not been reported due to the complexity involved in anisotropic elasticity. A new approach was attempted and analytical solutions were obtained. The stress expressions were used to prove the vanishing of long-range stress field of a low-angle tilting boundary in a cubic bicrystal. A paper is in preparation for publication (B2 in the list of reports).

(6) Grain Boundary Diffusion in Nb Bicrystals

Data of grain boundary diffusion in bcc bicrystals are not available in the literature. We have been investigating the grain boundary diffusion of pure chromium in niobium bicrystals with a $\Sigma 13$ CSL boundary. Eight samples were diffusion-annealed at six different temperatures and the concentration profiles were analyzed using a JEOL 733 superprobe. The results will be reported shortly (B4 in the list of reports).

CONCLUDING REMARKS

As mentioned in the above, there have been a number of technical difficulties encountered in the course of this investigation. The unexpected death of our colleague and collaborator, Dr. Norman Peterson, further weakened our efforts in diffusion study.

Fortunately, we were able to initiate and analyze a few related topics which are of basic importance in the development of the Ni_3Al system.

We hope that the work of grain boundary diffusion in Ni_3Al and other intermetallic alloys could continue to obtain more basic data for technological applications.

PERSONNEL

During the grant period, Dr. Y. T. Chou, Professor of Materials Science and Engineering, served as the principal investigator. He was assisted by Mr. B. Zhou and Mr. X. R. Qian. Mr. Qian, a visiting scholar from China, has been working on alloy softening effect and bicrystal growth. Mr. Zhou was engaged in bicrystal growth and diffusion work. In the third year of the program, Mr. X.M. Li participated in cation diffusion in oxide superconductors and subsequently in grain boundary diffusion in niobium bicrystals. Both Mr. Zhou and Mr. Li are Ph.D. candidates in the Department of Materials Science and Engineering.

LIST OF REPORTS AND PUBLICATIONS

(A) Reports published and accepted for publication

- (1)* "New Electrolytic Etchant for Dislocation Etch Pits in Ni_3Al Single Crystals," W. F. Qin and Y. T. Chou, *J. Less-Common Metals*, 139 p.283 (1988).
- (2)* "Boron Induced Softening in Polycrystalline Stoichiometric Ni_3Al Alloys," X. R. Qian and Y. T. Chou, *Materials Letters*, 6, p.157 (1988).
- (3)* "A Statistical Analysis of Microhardness Data in Boron Softened Ni_3Al ," X. R. Qian and Y. T. Chou, *Scripta Metallurgica*, 22, p.725 (1988).
- (4)* "Grain Boundary Softening in Boron-Doped Ni_3Al ," X. R. Qian and Y. T. Chou, *Proc. of the MRS Symposium on Interfacial Structure, Properties and Design*, edited by M. H. Yoo, C. L. Briant, and W. A. T. Clark, *Materials Research Society Press, Pittsburgh, PA., Vol. 722*, p.311, 1988.
- (5)* "The Effect of Boron on Microhardness in Ni_3Al Polycrystals," X. R. Qian and Y. T. Chou, *Proc. of the MRS Symposium on High Temperature Ordered Intermetallic Alloys*, edited by C. C. Koch, C. T. Liu, N. S. Stoloff, and A. I. Taub, *Materials Research Society Press, Pittsburgh, PA., Vol. 133*, p.529 (1989).
- (6)* "Uphill Diffusion in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Thick Film on Al_2O_3 Substrate," X. M. Li, Y. T. Chou, Y. H. Hu and C. L. Booth, *J. Materials Science Letters*, 9, 669 (1990).
- (7)+ "Cation Interdiffusion Between Thick Film of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ and Ceramic Substrate," X. M. Li, Y. T. Chou, Y. H. Hu and C. L. Booth, *J. Materials Science* (in press).
- (8)+ "Alloy Softening in Ni_3Al Polycrystals," X. R. Qian and Y. T. Chou, *J. Materials Science* (in press).

(B) Reports in preparation

- (1) "The Effect of Boron on Recrystallization and Grain Growth in Ni_3Al ," B.Z. Zhou, S. Z. Yu, Y. T. Chou and C. T. Liu, for the Sixth Int. Symposium (JIMIS-6) on Intermetallic Compounds - Structures and Mechanical Properties, 1991.
- (2) "Grain Boundary Dislocations in a Bicrystal of Cubic Symmetry," Y. T. Chou, to be submitted to *Philosophical Magazine*, 1991.

- (3)+ "Hardness Anisotropy and Alloy Softening in Ni_3Al Single Crystals," X. R. Qian and Y. T. Chou, to be submitted to Metallurgical Transactions, 1991.
- (4) "Grain Boundary Diffusion of Chromium in Nb Bicrystals," X. M. Li, and Y. T. Chou, to be submitted to Acta Metallurgica and Materialia, 1991.
- (5) "Grain Boundary Diffusion in Ni_3Al Polycrystals Containing Boron and Hafnium," B. Zhou and Y.T. Chou.

The total number of reports and publications summarizing the results of the supported programs is thirteen (13).

* reprint attached ~~*~~

+ report attached ~~*~~

~~*~~ not included -

END

**DATE
FILMED**

4 / 02 / 92