USE OF ANOMALOUS SMALL ANGLE X-RAY SCATTERING
TO INVESTIGATE MICROSTRUCTURAL FEATURES IN COMPLEX ALLOYS

Technical Progress Report
for period July 1, 1987 - July 31, 1988

J. R. Weertman, Principal Investigator
Professor of Materials Science and Engineering

Northwestern University
Evanston, Illinois 60208

August 1988

THE U. S. DEPARTMENT OF ENERGY
UNDER CONTRACT DE-FG02-86ER45229

N O T I C E

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

MASTER

TECHNICAL PROGRESS REPORT FOR THE PERIOD

JULY 1, 1987 TO JULY 31, 1988

This report covers the last 5 months of the second year of this grant and the first 8 months of the third year. The research thrust of this grant has been directed into two areas. The principal effort has been spent in an investigation of the use of anomalous small angle x-ray scattering (ASAXS) to observe changes in the microstructure of a relatively complex alloy produced by high temperature deformation or aging. The second effort involves a study of the high temperature behavior of several ferritic steels. During this past year we have been examining the effect of environment (air vs vacuum) on the high temperature strength of Fe9Cr1Mo modified by the addition of small amounts of V and Nb.

1. Anomalous Small Angle X-ray Scattering

Anomalous small angle x-ray scattering offers the possibility of separating out the scattering caused by a particular scattering entity from the total scattering in a complex material containing a number of scattering systems. Thus it may be possible to follow the influence of various forms of high temperature service (simple aging, creep, cyclic stresses) on the different carbides or other precipitates in an alloy such as the modified Fe9Cr1Mo. With the use of a synchrotron for the source of radiation it is possible to obtain a monochromatic beam of x-rays which can be tuned over a wide range. Therefore it is possible to take advantage of the phenomenon of anomalous scattering to separate out the contribution to the total scattering from the various scattering species.

Of necessity, this last year has been devoted to design and

construction of the new SAXS camera to be used in the anomalous x-ray scattering measurements since both the National Synchrotron Light Source (NSLS) at Brookhaven National Lab and CHESS at Cornell have been closed down. However NSLS is now starting to operate, and we have just heard that our proposal for beam time (for this work) has received one of the very highest ratings. Therefore we hope to be resuming measurements shortly.

During this period when trips to the synchrotron facilities were impossible we have been redesigning and constructing the SAXS camera. This is being done in collaboration with Dr. Gabrielle Long of NBS. NBS has furnished a considerable fraction of the components of the camera, and we are using the NBS beam line at NSLS. The camera is a compact device which is similar in design to that of Bonse and Hart (Z. Phys. 189 (1966) 151). The following improvements have been made in our camera:

- * Use of multiple Bragg reflections to reduce the instrumental function below the SAXS curve at higher angles.
- * Asymmetrically-cut crystals to achieve better collimation of x-ray beam and magnification of beam area on the sample. The asymmetric cut allows the harmonics of the Bragg reflection to be "tuned" out, thereby providing a beam which is more nearly monochromatic.
- * Portable design allows us to use this camera at synchrotron radiation sources as well as at conventional laboratory sources such as x-ray tubes and rotating anodes.

In February Pete Jemian, the graduate student working on this project, spent a week at NBS checking out the hardware. We have purchased a

MacIntosh PC, and he has interfaced this with the data acquisition computer at the beamline. We will now be able to analyse and plot the newly acquired data as they are taken and immediately note any errors or changes that need to be made in the measurements being taken. The PC will be brought back to Northwestern for more detailed analysis of the data after completion of the synchrotron measurements. Pete currently is developing a software routine for desmearing the data. He also is about to finish developing and building the circuit for the new x-ray detector. This silicon photodiode detector has a remarkably wide linear dynamic range (11 orders of magnitude) and at the upper end can measure the unattenuated beam. Used with monochromatic radiation (as in the present case) the detector allows the direct calculation of absolute intensity. The detector's wide linear range eliminates the need for the collection of many overlapping sets of data taken with various thicknesses of attenuating foils, in order to cover the whole range in scattering vector. Such overlapping is a source of error in the results. The need for a separate scan to calibrate for absolute intensity also is eliminated.

This camera has been constructed as part of a program to relate the mechanical behavior of an engineering alloy to its microstructural evolution. By using small angle scattering in combination with the effect of anomalous dispersion the SAXS curve from an alloy with multiple precipitate types may be decomposed into the individual SAXS curves of each precipitate type. In order for the experiment to be successful it is necessary to make a careful choice of the alloy to be measured. Initially we proposed to use this technique on the alloy Fe₉Cr₁Mo₁V₁Nb₁, which is used

in high temperature power generation applications. However calculations indicate that a better choice for an alloy to be studied is the high strength, high toughness steel AF1410 ($\text{Fe}_{14}\text{Co}_{10}\text{Ni}_2\text{Cr}_1\text{Mo}$). Using ASAXS, we intend to follow the transformation of the Fe-rich M_3C into Cr-rich M_2C as a function of aging and fatigue at high temperatures. The experiment at the synchrotron would involve measuring the SAXS from the alloy at several wavelengths just above the K-shell absorption edge wavelength of chromium. Figures 1 and 2 show the scattering to be expected from the M_2C and M_3C carbides and from voids associated with the carbides, produced by the onset of ductile fracture during deformation. The calculations were based on estimates of the approximate size, volume fraction and chemical composition of the carbides from TEM studies carried out by the group of Professor G. Olson. Figures 3 and 4 show the expected changes in the scattering produced by working close to, and a little back from the chromium K edge. The changes come primarily from the chromium-rich M_2C carbides. Thus the differences in the curves represent the scattering from the M_2C carbides alone. From this scattering information an average size and the number density of the two carbide species can be calculated and thus the transformation and coarsening followed. Void damage in deformed specimens also can be observed.

Plans for the Balance of the Grant Year (ASAXS)

The upgrade of the circuitry for the photodiode detector will be completed and tests carried out in the x-ray facility at Northwestern. We are currently working on the sensitivity at the low intensity end of the

SAXS from each scatterer in Fe-14Co-... Steel

9 March 1988

Fig. 1. Calculated scattering intensity as a function of scattering vector from the M_2C , M_3C carbides and voids in Fe14Co10Ni2Cr1Mo.

predicted SAXS from Fe-14Co-... Steel

9 March 1988

Fig. 2. Calculated scattering intensity as a function of scattering vector from both carbide species and from the carbides and voids.

predicted ASAXS of Fe-14Co-... Steel

9 March 1988

Fig. 3. Calculated changes in the scattering intensity vs scattering vector at various wave lengths near the K edge for Cr. No voids present.

Guinier plot of predicted SAXS data

9 March 1988

Fig. 4. Guinier region of Fig. 3.

detector, so that we can extend the range of the SAXS camera to higher scattering angles where the count rate is very low. The detector already is very satisfactory at the high and middle ranges. We also must prepare the very thin samples required for the measurements. It is not a trivial problem to produce such thin samples with a reasonably uniform thickness over the extent of the beam area.

We expect to go to NSLS this fall to conduct shakedown experiments during the 5 days of "feasibility time" on the NBS beam that Dr. Long has available to her. At the present time we are expecting about 7 days of regularly scheduled beam time before the end of the year and about 10 days between January and April. Therefore we expect shortly to be making scattering measurements and analysing the data..

To verify the ASAXS results and to assist in their interpretation, we plan to carry out extensive TEM examination of the microstructure of the samples, especially focussing on the size and composition of the carbides. The TEM experience of Dr. Gavillet will be invaluable in this work.

2. Environmental Softening of Modified Fe9Cr1Mo at High Temperatures

Early in the study of the high temperature fatigue behavior of the Fe9Cr1Mo steel there were repeated indications that the samples tested in air underwent greater softening than those tested in vacuum. This interesting observation led to the experiments which formed the basis of J. Hollar's masters thesis. The newest student on the project, Rena Hecht, was to have investigated the cause of this softening for her PhD thesis. Dr. Gavillet also worked on the investigation when he arrived from

Switzerland. He was instrumental in discovering the explanation of the effect.

From a series of tests with dummy samples containing holes to accommodate a number of thermocouples, it was found that in air a significant temperature gradient exists along the length of the specimen (Fig. 5). Whereas the temperature is quite uniform in vacuum, in air convection currents raise the temperature of the upper end of the specimen relative to that of the lower. The extent of the gradient is somewhat surprising in view of the baffles and radiation shields around the specimen. The thermocouple which controls the furnace is generally placed just below the diametral extensometer at the waist of the sample. Therefore the key portion of the sample which controls its measured mechanical behavior, i.e., the narrowest part, is hotter in air than in vacuum for the same furnace setting. Tests have shown that this difference in temperature is enough to account for the observed softening. Thus the explanation for the so-called environmental softening effect is quite banal, and this part of the project has been abandoned.

Plans for the Balance of the Grant Year

In keeping with a general theme of this project, high temperature mechanical behavior/microstructural changes/damage accumulation/environmental interactions, all with a strong emphasis on characterization, we plan to study the earliest stages of surface damage and note its evolution into cracking. The effect of environment (air vs vacuum) will be examined as well temperature and fatigue parameters.

Besides the usual tools of SEM and TEM (with replicas) to study

Figure 5 : Temperature along the vertical axis of the specimen during air and vacuum deformation.

surface damage, we plan to use a scanning tunneling microscope for very high resolution (on the order of atomic distances) as well as for lower resolution study of the earliest stages of strain localization and cracking. Professor Chung of our Department has made several STMs and is using them for tribology and fatigue studies. We have almost completed construction of our own STM and software. It was designed to study surface features of fatigued and crept samples. We believe that with the high resolution information furnished by the STM, together with SEM observations, and TEM studies of the associated dislocation structures, new information on the high temperature fatigue failure process in the Fe9Cr1Mo and similar steels will be forthcoming.

Statement of Effort

The Principal Investigator is devoting 15% of her effort during the academic year to this project. During the summer 25% of her time is being devoted to it. Graduate student Pete Jemian is primarily working on the ASAXS measurements. He has been admitted to PhD candidacy. Dr. Gabrielle Long is on his examining committee. Rena Hecht now is a second year PhD student. She is working on the fatigue damage experiment. Dr. Gavillet, who, like the graduate students is devoting 100% of his time to the project, is partially supported by the Swiss Federal Reactor Institute. He is involved with the damage/STM work and also will be contributing to the scattering studies.

Publications (Copies are included in this report.)

"Investigation of Microstructural Changes in a Ferritic Steel Caused by High Temperature Fatigue", S. Kim and J. R. Weertman, Metallurgical Transactions A, 19A (1988) 999-1007.

"Surface Oxide Film Softening in a Ferritic Steel at Elevated Temperature", J. Hollar and J. R. Weertman, Scripta Metallurgica, 21 (1987) 1577-1580.

Oral Presentation

"Effect of Environment on the Cyclic Strength of a Ferritic Steel Fatigued at Elevated Temperature", J. Hollar and J. R. Weertman, Fall 1987 TMS-AIME Meeting, Cincinnati, OH.

END

**DATE
FILMED**

3 / 23 / 92