DOE/PC/90044--4

DE92 004519

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Technical Progress Report for the Period

July 1, 1991-September 30, 1991

Kamil Klier and Richard G. Herman
with
Marie Johannson, Owen C. Feeley,
Steve Bogar, Edward Lawson, and Mark Kieke

Zettlemoyer Center for Surface Studies
and Department of Chemistry
LEHIGH UNIVERSITY
Bethlehem, PA 18015

MASTER

November 1991

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

PREPARED FOR THE

U. S. DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER

Contract No. DE-AC22-90PC90044

Received by OSTI
DEC 30 1991

WOM

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

OBJECTIVES OF THE RESEARCH

The objective of the proposed research is to synthesize high octane ethers, primarily methyl isobutyl ether (MIBE) and methyl tertiary butyl ether (MTBE), directly from $H_2/CO/CO_2$ coal-derived synthesis gas via alcohol mixtures that are rich in methanol and 2-methyl-1-butanol (isobutanol). The overall scheme involves gasification of coal, purification and shifting of the synthesis gas, higher alcohol synthesis, and direct synthesis of ethers.

The last stage of the synthesis involves direct coupling of synthesis gas-derived methanol and isobutanol that has been demonstrated by us to occur over superacid catalysts to yield methyl isobutyl ether (MIBE) at moderate pressures and a mixture of methanol and isobutene at low pressures. MIBE is an isomer of MTBE and a process is proposed whereby MTBE from the two alcohols is maximized and MIBE is minimized. This will be achieved by the proper choice of reaction conditions, i.e. intermediate pressures, and of inorganic acid catalysts that are stable at temperatures higher than 200°C, at which the carbonium ion reaction coupling of the two alcohols to MTBE is more effective than the oxonium ion or ester reaction coupling to MIBE.

Both organic and inorganic catalysts will be investigated, and the better catalysts of these classes will be subjected to long term performance studies. The long term performance studies of the combined process will extend to 1000 hr and detailed analytical data for all products will be provided. The project is divided into the following three tasks:

- Task 1. Synthesis of High Octane Ethers from Alcohol Mixtures Containing Predominantly Methanol and 2-Methyl-1-Propanol over Superacid Resins

Task 2. Inorganic Catalysts for the Synthesis of High Octane Ethers
from Alcohols

Task 3. Long Term Performance and Reaction Engineering for Scale-Up
of the Alcohols-to-Ethers Process

The expected result of the proposed research is a novel process for producing ethers, in particular MTBE, in which all five carbons of the unsymmetric C_1 -O- C_4 ethers originate from coal-derived synthesis gas.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

SUMMARY OF TECHNICAL PROGRESS

The analytical methodology used for product analyses was reassessed. The reactant and major product thermal response factors of the gas chromatograph were recalibrated. The identification of products was confirmed with GC-MS analysis. The assessment verified previous data and optimized quantification of the products formed over the acid catalysts being tested for the coupling of alcohols to form ethers and for the formation of MTBE from isobutene and methanol.

The activities of three acidic ion exchange resins, Amberlyst-15, Purolite 150, and BioRad AG 50WX2, for the production of MTBE from isobutene and methanol were tested at 75°C and 1 atm in the vapor phase in a flow reactor using 0.25 g of catalyst. The Amberlyst-15 commercial catalyst, as well as Purolite 150, was active with 100% selectivity to MTBE. The Amberlyst catalyst was found to be more active than the Purolite. The BioRad sample, although acidic, was completely inactive for the reaction under these conditions. In addition, the Purolite catalyst was tested over the temperature range of 75-105°C, and the effect of varying reactant space velocity over Purolite at 75°C was also determined.

A standardized test for the coupling of methanol and isobutanol was developed to systematically screen solid acids for catalytic activity and selectivity. The test reaction uses 5 g of catalyst at 90°C under a total pressure of 1 atm. The molar ratio of methanol to isobutanol in the feed is 1:1. The flow rate of each alcohol is 1.72 mol/kg cat/hr and that of helium and nitrogen is 16 mol/kg cat/hr. The catalysts used in this phase of testing were all acidic ion exchange resins: Amberlyst-15, BioRad AG 50WX2, Nafion-H

microsaddles, and Purolite 150. The order of activity of the catalysts was determined to be Amberlyst = Purolite > BioRad > Nafion. Several ethers were produced with MIBE predominating, particularly in the case of Nafion.

Characterization of the organic resins was carried out in terms of swelling properties of the resins in water and in methanol and accessible ion exchange capacity of the resins as measured by the exchange of the H^+ groups with Na^+ after drying and then swelling in water or methanol.

TECHNICAL PROGRESS

A. Calibration of Thermal Response Factors and GC Parameters

Thermal response factors (TRF) are necessary to quantitatively calculate amounts of products from the raw peak areas in gas chromatographic analysis when a thermal conductivity detector (TCD) is used. The raw peak area is divided by the thermal response factor to give the true response value.

Thermal response factors used in previous reports have not been determined in this laboratory, but literature values for reactants and products, as listed by Dietz (1), were utilized. However, it was found that the values from Dietz were not always satisfactory. As the TCD is the main detector for analyzing reactor effluent, it is very important that thermal response factors are correct. New thermal response factors have been determined for methanol, isobutanol, methyl tert-butyl ether, dimethylether, and isobutene.

Experimental

To avoid any interference from catalytic activity, the reactor was filled with only 3 mm glass beads. Calibration was carried out at 123°C and ambient pressure. According to Dietz (1), thermal response factors are independent of temperature and flow rate. The flow of the internal standard, N₂, was carefully determined by several measurements using a bubble meter. Either dimethylether (DME) or isobutene was added and the total flow was measured. Liquid samples such as methanol (MeOH), isobutanol or methyl tert-butyl ether (MTBE) were introduced via a Gilson pump at a rate of 12.0 µl/min. Finally, helium, an inert carrier, was added to give a total flow of 5-6 L/hr.

Steady-state was reached within a 2 hr period and the calibration was allowed to run overnight to get a longtime average. Flows were very stable and the difference from injection to injection was kept to a minimum.

Results

The new thermal response factors (TRF) are determined in reference to the internal standard. This approach assumes that the thermal response factor for nitrogen is correct. Nitrogen is a common internal standard in GC analysis, and therefore this assumption was accepted for this application. As can be seen from Table I, the new thermal response factors are increased for isobutene and isobutanol by 13 and 19 percent respectively, the thermal response factor for methanol is decreased by 9 percent. The largest change was measured for dimethylether, which dropped 25 percent. The value for MTBE only changed by a difference of two units, which is within experimental error. Thermal response factors are not absolute values, rather they are instrumental values that will differ from system to system. It is also important to recognize that there is an age factor involved, meaning it is likely that the thermal response factors will change over time as the TCD ages. The new values for thermal response factors are used throughout this report and will be continued to be used in the future.

Gas Chromatographic Parameters

In a previous report (2), parameters for gas chromatographic separation were listed. However, to further improve separation of the products, the temperature program was modified and the length of each analytical separation run was increased. The same column initially installed is still utilized. The column is a Wall Coated Open Tube (WCOT) capillary column with a chemically bonded 5.0 μm thick methyl silicone coating purchased from Chrompack Inc.

Table I Thermal Response Factors

Compound	New TRF	Old TRF
MeOH	50	55
isobutanol	115	97
MTBE	127	125
DME	75	100
isobutene	93	82

Operating Conditions

The development of new operating parameters is an ongoing process and will continue when necessary. The operating parameters used currently are listed in Table II.

These "new" conditions allow for separation of isobutene from both 1-butene and 2-butene. These three products are also separated from methanol and DME. Several iso-octenes can be separated from each other, but exact identification of the iso-octenes has yet to be resolved. C-8 ethers such as ditertiary butyl ether (DTBE) and diisobutyl ether (DIBE) can be resolved from one another as well as from the iso-octenes. The chromatogram is not very well resolved towards the higher weight products, meaning after approx. 16 min, but two distinct groups of peaks can be seen. These groups are believed to be different kinds of C-12 compounds, and GC-MS will give a more complete identification of these products.

Table II Present GC conditions

Column pressure	5 atm
Injector temperature	250°C
Detector temperature	275°C
Oven conditions:	
Initial temperature	50°C
Initial time	2 min
Temp. ramp A	8°C/min to 110°C
Hold time at 110°C	0 min
Temp. ramp B	20°C/min to 250°C
Hold time at 250°C	9 min
Total analysis time	25 min

B. Gas Chromatographic Analysis with Mass Spectrometric Detection

Mass spectrometry is very useful in conjunction with gas chromatographic separation. It has the power of obtaining many spectra within a chromatographic peak, which can be used for detecting the products in unresolved GC peaks. It also serves as a more or less absolute indication of substances present in a mixture.

Experimental

Reaction products from a standard test over Amberlyst-15 were cold trapped and stored in a sealed container. The sample was analyzed by GC-MS using a similar column as mentioned above and the same operating conditions.

Results

Attention was focused on resolving methyl tertiary butyl ether (MTBE) from methyl isobutyl ether (MIBE) and ditertiary butyl ether (DTBE) from diisobutyl ether (DIBE). No C-12 compounds were present in this sample. MTBE and MIBE show very different splitting pattern in mass spectrometric analysis and therefore distinction between the two was unambiguous.

The mass spectrum of DIBE showed a perfect fit with the library spectra and is therefore determined beyond any doubt. However, the peak in the chromatogram

that is assigned to DTBE does not show an unambiguous fit with the library spectrum. Instead the mass spectra indicate that it could be DTBE or the mixed ether isobutyl tertiarybutyl ether. There is also a possibility that the column is not able to separate the two ethers so that they are both contained in the same peak. This can be resolved by taking several spectra within the "DTBE" peak. Until this is solved the peak will still be assigned as DTBE.

C. MTBE Synthesis from Methanol and Isobutene

The present commercial process for the production of MTBE involves the liquid phase addition of methanol to isobutene over the acidic ion exchange resin Amberlyst-15 in the temperature range of 50-90°C. We have initiated a limited study of this reaction over several acidic ion exchange resins in the vapor phase. This capability provides us with a useful way to compare the relative activity of our catalysts toward MTBE production. This reaction is also believed to be important in the coupling of methanol and isobutanol in which the acid catalyzed dehydration of isobutanol to isobutene may be followed by methanol addition to the isobutene to yield MTBE. The conditions chosen for this reaction were based on those used by Baba et al. (5):

Catalyst Weight	0.25 g (dry)
Temperature	75°C
Total Pressure	1 atm
N ₂ /He:MeOH:i-Butene	2:1:1
Space Velocity	0.5 mol gas/g cat/hr

The acidic ion exchange resins used in this study were Amberlyst-15, Purolite 150, and BioRad AG 50WX2. The Amberlyst was obtained in dry form from the manufacturer and was used without pretreatment. Both of the Purolite and

BioRad resins were in an extremely wet form originally and had to be dried at 90°C overnight prior to loading the reactor. The catalyst bed was diluted with 3 cm³ of Pyrex beads. The flow system and analysis used for these reactions have been described previously. The results of the MTBE synthesis over these catalysts using the conditions listed above are given in Table III. The most striking aspects of these results are that the macroreticular resins Amberlyst and Purolite were active while the gel-type resin BioRad was completely inactive. The macroreticular resins are characterized by a rigid structure with well-defined pores that allow easy access to internal acid sites for most liquid and vapor phase organic molecules (4). The gel type resins are produced in a manner that results in a structure that is inherently *nonporous* (4). Gel-type resins will swell when exposed to liquid phase polar solvents, such as alcohols. This swelling opens the interior of the resin particle to reactants (4,5). The literature shows that gel-type resins are active in liquid phase reactions, but are poor catalysts for vapor phase reactions (5, 6). The MTBE synthesis reactions also show that the commercially used catalyst Amberlyst-15 is more active on a weight basis than Purolite. Both Amberlyst-15 and Purolite are 100% selective towards MTBE formation with no trace of other products.

Purolite Temperature Dependence

After finding that Purolite is an active and selective MTBE catalyst, some additional tests were performed in order to ascertain its activity profile with respect to temperature and reactant gas hourly space velocity. The steady state activity of Purolite at temperatures between 75-105°C under the same conditions as those used above for the MTBE synthesis are given in Table IV. The maximum yield of MTBE is found at 85°C.

Table III

Results of Methanol and Isobutene Coupling

Pressure: 1 atm
 Temperature: 75°C
 Total flow; Purolite = 1951.2 mol/kg/hr
 Biorad = 1974.4 mol/kg/hr
 Amberlyst-15 = 2015.8 mol/kg/hr

<u>Catalyst</u>	<u>Feed</u> (mol/kg/hr)	<u>Yield</u> (mol/kg/hr)	<u>Conversion</u> (%)
Purolite 0.2559 g	MeOH = 489.7 i-Butene=486.2	MTBE = 76.6	15.8
Biorad 0.2587 g	MeOH = 484.4 i-Butene=466.5	MTBE = 0.0	0.0
Amberlyst-15 0.2526 g	MeOH = 496.1 i-Butene=493.8	MTBE = 121.4	24.6

Space Velocity Dependence over Purolite

The results of varying reactant space velocity over Purolite at 75°C is presented in Table V. The activity of the catalyst responds quite well to changing space velocity. Starting with a reactant space velocity of about 500 mol/kg cat/hr, the conversion was 36%. Doubling the space velocity essentially decreased the conversion by half to 15.5%. Doubling the space velocity once more again decreased the conversion by approximately half to 7.4%.

D. Ether Synthesis via Coupling of Methanol and Isobutanol

The course of this work will include testing of various solid acid catalysts for the direct coupling of methanol and isobutanol to ethers. The first stage of catalyst testing involves the use of commercially available acidic ion exchange resins and is discussed below. The second stage of catalyst testing

Table IV

Results of methanol and isobutene coupling
over Purolite as a function of temperature

Pressure: 1 atm
Catalyst weight: 0.26g

<u>Temperature</u>	<u>Feed</u> (mol/kg/hr)	<u>Yield</u> (mol/kg/hr)	<u>Conversion</u> (%)
75°C	MeOH = 489.7 i-Butene=471.8 N ₂ /He = 969.9	MTBE = 72.6	15.4
85°C	MeOH = 489.7 i-Butene=471.8 N ₂ /He = 969.9	MTBE = 90.5	19.2
95°C	MeOH = 489.7 i-Butene=471.8 N ₂ /He = 969.9	MTBE = 79.9	16.9
105°C	MeOH = 489.7 i-Butene=471.8 N ₂ /He = 969.9	MTBE = 65.8	14.0

Table V

Results of methanol and isobutene coupling over Purolite 150
as a function of reactant space velocity

Pressure: 1 atm (761.6 mm Hg)

Temperature: 75°C

Catalyst weight: 0.25g

<u>Run</u>	<u>Feed</u> (mol/kg/hr)	<u>Conversion</u> (%)
Low	MeOH = 243.4 i-Butene=267.1 N ₂ /He = 485.3	36.0
Medium	MeOH = 488.5 i-Butene=486.2 N ₂ /He = 975.3	15.5
High	MeOH = 977.2 i-Butene=957.1 N ₂ /He = 1958.4	7.4

will involve the use of various inorganic solid acids including zeolites, clays, oxides, silica-alumina and γ -alumina. The ion exchange resins studied were Amberlyst-15, BioRad, Nafion-H microsaddles, and Purolite. All except Nafion-H were sulfonated forms of polystyrene with divinyl-benzene crosslinking. Amberlyst-15 and Purolite are macroreticular forms of the polystyrene type resins. BioRad is described by its manufacturer as a purified form of the Dowex 50W-X2 gel form of polystyrene resin. Nafion-H is a copolymer of tetrafluoroethylene and fluorinated vinyl ethers that contain fluorosulfonyl groups.

Standardized Test for Direct Coupling of Alcohols to Ethers

In order to study the coupling of methanol and isobutanol to ethers in a systematic manner, it was found necessary to develop a standardized set of reaction conditions. Thermodynamic calculations of the direct coupling of methanol and isobutanol indicate that low temperatures, i.e. 50-90°C, are necessary to achieve favorable selectivity to desired products, especially MTBE and MIBE. All of the ion exchange resins are thermally stable within this temperature range, and 90°C was chosen for the reaction temperature in order to maximize conversion. Low pressure, i.e. 1 atm, is utilized in these reactions in light of the findings of Nunan et al. (7) that indicated lower pressures resulted in more isobutene formation, the precursor of MTBE. The alcohol partial pressure was chosen such that no condensation would occur within the reaction system, and this was determined empirically under reaction conditions. The ratio of methanol to isobutanol used in the feed was investigated using Amberlyst-15 as a catalyst. Initially, a molar ratio of MeOH:i-BuOH = 2:1 was used for the feed. Then the same experimental conditions were used except that the MeOH:i-BuOH ratio was changed to 1:1, which is the stoichiometric ratio of the desired reaction. The 1:1 reactant mixture yielded more ether products than the 2:1 mixture, so the 1:1 molar alcohol ratio was chosen for the standard test

reaction. Alcohol feed rate and total gas flow were similar to those described in Nunan et al (7). The catalyst bed was diluted to 20 cm³ with Pyrex beads.

A summary of the experimental conditions is given below:

Catalyst weight	5.00 g (dry)
Reaction temperature	90°C
Total Pressure	1 atm
Molar ratio MeOH:iBuOH	1:1
MeOH flow rate	1.72 mol/kg cat/hr
iBuOH flow rate	1.72 mol/kg cat/hr
He + N ₂ flow rate	16 mol/kg cat/hr

Product Analysis

The acid catalyzed reaction of two alcohols usually results in a complex mixture of products. As a reminder the following product abbreviations are used in this report:

DME: Dimethyl ether
MTBE: Methyl tert-butyl ether
MIBE: Methyl iso-butyl ether
DTBE: Di-tert-butyl ether
DIBE: Di-iso-butyl ether

The sources of these products are as follows:

- 1) $2 \text{ MeOH} \longrightarrow \text{DME} + \text{H}_2\text{O}$
- 2) $\text{MeOH} + \text{i-BuOH} \longrightarrow \text{MTBE} + \text{H}_2\text{O}$
or
- 3) $\text{MeOH} + \text{i-Butene} \longrightarrow \text{MTBE}$
- 4) $\text{MeOH} + \text{i-BuOH} \longrightarrow \text{MIBE} + \text{H}_2\text{O}$
- 5) $\text{i-Butene} + \text{t-BuOH} \longrightarrow \text{DTBE}$
- 6) $\text{i-Butene} + \text{i-BuOH} \longrightarrow \text{DIBE}$
or
- 7) $2 \text{ i-BuOH} \longrightarrow \text{DIBE} + \text{H}_2\text{O}$

The i-butene and t-BuOH that are present in some of the above reactions come about from the original i-BuOH reactant:

In addition, the acid catalyzed dehydration of isobutanol has been studied by several workers and is known to result in a mixture of butenes, i.e. i-butene, 1-butene, and 2-butene (8, 9).

Mechanistically, reactions 1, 2, 4, 7, and 8 involve oxonium ion intermediates. Reactions 3, 5, 6, and 9 require carbenium ions to be formed.

Activity and Selectivity of Ion exchange resins

The results of the standard test over the four ion exchange resins at steady state activity are shown in Table VI.

Table VI

Activities of Catalysts for MeOH + i-BuOH Standard Test

Conditions:

Pressure 1 atm
Temperature 90°C

Catalyst	Methanol Conversion Percent	Isobutanol Conversion Percent
Amberlyst-15	9.1	10.2
BioRad	4.9	5.4
Marion MS	1.4	1.4
Purolite	9.2	9.9

All runs reached steady state after the first hour of reaction. All catalysts studied were most selective for MIBE production. Relative overall

activity followed the order Amberlyst $\approx$ Purolite > BioRad >> Nafion. One interesting observation is that BioRad is quite active in the reaction between methanol and isobutanol but was observed to be inactive for methanol and isobutene conversion. The presence of isobutanol at a temperature much below its boiling point may allow it to be adsorbed enough by the BioRad gel resin to cause swelling and thus access to active sites in the interior of the resin particle, thus possibly explaining the sharp difference in its activity with different reactants. Product selectivities for the different catalysts are illustrated by Figure 1. Water, which is, of course, the major product of these dehydration reactions, is not included in the selectivity analysis. Under the standard reaction conditions, Nafion-H appears to be the best catalyst for MIBE production. The other catalysts produce significant amounts of MTBE, along with the other ethers DTBE, DIBE, and DME. The higher selectivity of Nafion towards MIBE formation may be due to the distinctly different nature of the acid sites of Nafion. The fluorosulfonic acid groups of Nafion contrast with the sulfonic acid groups of the other ion exchange resins tested in this study. Figure 2 gives the ratios of i-butene to MTBE and DME to MIBE produced over the catalysts and illustrates the effectiveness of the catalysts for MTBE formation. A high i-butene/MTBE ratio in the case of Nafion suggests that even when i-butene is formed in relatively high concentrations in the presence of excess methanol, it is difficult to produce MTBE.

Because the formation of every mole of the dibutyl ethers, DTBE and DIBE, requires the consumption of two moles of isobutanol, a more useful assessment of selectivity may be that based on moles of carbon in the product. The carbon weighted selectivities, which it must be noted emphasize the higher ethers and butenes but de-emphasize DME, are presented in Figure 3.

FIGURE 1

Selectivity

Mol % of products

Water excluded

FIGURE 2
Product ratio for standard test

FIGURE 3

Selectivity

Mol % Carbon

Work in Progress

The second phase of catalyst testing that makes use of inorganic solid acids has begun. The use of the thermally stable inorganic materials allows reaction temperatures to be much higher than the decomposition points of the ion exchange resins. Indeed, preliminary results show that somewhat higher temperatures are needed for activity in the alcohol coupling reaction.

A relatively pure sample of MIBE has been synthesized following method 2 described in the first quarterly report of this project. Fractional distillation resulted in MIBE that was 96% pure as analyzed by gas chromatography. The only major impurity found was isobutanol. Samples of this synthesized MIBE, as well as a 50:50 mixture of MIBE with commercially available MTBE (Aldrich), has been sent to Amoco Research Center in Naperville, IL for octane rating testing.

E. Characterization of the Organic Resins

The commercial acidic organic resins were characterized by ion exchange titrations and volume swelling experiments. The particular resins investigated were the following:

1. Nafion-H 511 powder, duPont
2. Dow fluorinated sulfonic acid resin (FSA), Dow Chemical Co.
3. BIO-RAD AG 50W X-2, BIO-RAD Laboratories
4. Amberlyst-15, Rohm and Haas Chem. Co., distributed by Aldrich Chem. Co.
5. Purolite C-150, C-100x10, and C-100x10H, Purolite Co.

The Nafion-H fluorocarbon sulfonic acid resin is a copolymer of tetrafluoroethylene and fluorinated vinyl ethers, and its chemical formula has been schematically described in an earlier technical report. The Dow FSA resin is similar to Nafion-H, but with shorter fluorocarbon crosslinking chains between the resin backbone and the sulfonic acid groups. Both the Nafion-H and Dow FSA resins are more thermally stable than are the other organic resins. Amberlyst-15 is a copolymer of styrene crosslinked with divinylbenzene having sulfonic acid as its active acid exchange site and having a highly porous macroporous structure. The Purolite resins are similar to Amberlyst-15, being copolymers of styrene crosslinked with divinylbenzene. The C-100x10 and C-100x10H Purolites are reported to have 10% divinylbenzene crosslinking. The C-150 resin is not as highly crosslinked and is classified as macroporous, and it is reported to have a higher chemical and physical stability than the other Purolite resins. The C-150 and C-100x10 resins were received in the Na^+ form, while the C-100x10H was received in the H^+ form. The BIO-RAD AG 50W X-2 resin is a purified Dowex-50 resin that is a polystyrene sulfonic acid resin having a large effective pore size, and it was received in a very wet form and completely swollen with water.

Experimental Treatments

The process of testing the resins began with drying the resins to obtain a dry uniform starting weight. The resins were dried in an oven at 100-110°C for 2-6 hr, and then the resins were removed from the oven and allowed to cool in a CaSO_4 -containing dessicator.

Swelling experiments were carried out using methanol and water as swelling agents in a 10 ml graduated cylinder. A specified amount of resin (1-3 g) was measured into the cylinder, and 4-10 ml of solvent as added to the resin. After an equilibration time of 5-10 min, the final volume of the resin was measured. Calculation of %swelling was carried out by dividing the volume of the swollen resin by the initial volume of the dry resin and multiplied by 100.

The ion exchange test involved titration of the H-form of the resins with standardized NaOH. After the swelling measurement, the resin was transferred to a 100 ml beaker with ≈ 25 ml of the solvent. It was then titrated with the standardized NaOH solution while the pH of the solution was being continuously monitored by means of a Markson Model 88 digital pH meter with a combination electrode. Continuous stirring of the solution was carried out by means of a Sargent magnetic stirrer. Graphical plots of pH vs vol of NaOH added exhibited very clear endpoints, which were indicated by the midpoint of the steeply rising portion of the curve. The ion exchange capacity (excessable H^+ ion content) was calculated in meq/g or eq/l by the following equations:

$$(\text{vol NaOH})(\text{M NaOH})/\text{g resin} = \text{meq/g}$$

$$(\text{vol NaOH})(\text{M NaOH})/\text{l resin} = \text{eq/l.}$$

Comparisons of the manufacturers values were made, and it was found that more reproducible values could be obtained in some cases by carrying

out the ion exchange titration in dilute NaCl solution and by insuring that the starting resin was in the H-form by pretreatment of the resin with 1 M HCl. The pretreatment was carried out by placing the resin on filter paper in a funnel and allowing the acid to flow through the resin, which was followed by rinsing the resin with distilled water to remove excess acid.

Results and Discussion

The swelling tests showed that all of the resins exhibited moderate to severe swelling. As shown in Figure 4, the Purolite and Amberlyst-15 resins swelled to about the same extent, i.e. 45-65%, except for the swelling of Purolite C-100x10 in methanol. The other resins swelled to a much greater degree, corresponding to increases in volume of 2 to 4 times the initial dry volume. The swelling properties of the resins are important to consider when filling the reactor. Space must be allowed for expansion of the resins, and in our experiments Pyrex beads were used as a diluent with the resins so that void space was available for expansion of the resins.

The experimental ion exchange titration curves exhibited very sharp endpoints, as shown in Figures 5-14. Comparisons with the capacities given by the manufacturers, shown in Table VII, demonstrated that the acid sites were readily accessible to the exchanging Na^+ ions in most cases. However, it appeared that $\approx 20\%$ of the reported ion exchange sites of the BIO-RAD AG 50W X-2 resins were not titrated by the procedure utilized here, and this might have been due to the drying procedure used to achieve a reproducible weighed amount of the resin. It was observed that the Purolite resins tended to suffer osmotic shock upon using the drying process utilized here, i.e. that $\approx 5\%$ of the resin beads exhibited cracking due to extreme dehydration.

FIGURE 4 SWELLING OF THE ORGANIC RESINS

FIGURE 5

The Titration of Amberlyst-i5 (dry)
Swelled in Distilled Water using
0.4995M NaOH

FIGURE 6

The Titration of Amberlyst-15 (dry)
Swelled in MeOH using 0.4995M NaOH

FIGURE 7

The Titration of Purolite C-100x10H
(dry) Swelled in Distilled Water using
0.4995M NaOH

FIGURE 8
The Titration of Purolite C-100x10H
(dry) Swelled in MeOH using 0.4995M NaOH

FIGURE 9
The Titration of Purolite C-150
Swollen in Distilled Water using
0.5032M NaOH

FIGURE 10

The Titration of Purolite C-150
Swollen in MeOH using 0.5032M NaOH

FIGURE 11

The Titration of AG-50W-X2 (dry)
Swelled in Distilled Water using
0.4995M NaOH

FIGURE 12

The Titration of AC-50W-X2 (dry)
Swollen in MeOH using 0.4995M NaOH

FIGURE 13

The Titration of Nafion-511 (powder)
Swollen in MeOH using 0.1006M NaOH

FIGURE 14

The Titration of DOW FSA Swollen in
MeOH using 0.1006M NaOH

Table VII

Concentration of Acid Sites in the Resins From Ion Exchange Titrations. The Resins were Weighed After Drying and the Titrations were Carried Out After Swelling the Resins in Water or Methanol.

Resin name	Exper. Capacity	Manuf. Capacity	% error	Resin Preparation and Conditions
Amberlyst-15	4.59meq/g	4.7meq/g	2.34%	in H ₂ O, dried in a dessicator for 2 days
Amberlyst-15	4.58meq/g	4.7meq/g	2.55%	in MeOH, same as above
Amberlyst-15	4.63meq/g	4.7meq/g	1.49%	in H ₂ O, dried in a dessicator for 2 days, swelled in NaCl
Purolite C-100X10H	1.87eq/L	2.0eq/L	6.50%	in H ₂ O, dried at 100C 2 hrs.
Purolite C-100X10H	1.92eq/L	2.0eq/L	4.00%	in MeOH, dried at 100C 2 hrs.
Purolite C-150	1.65eq/L	1.9eq/L	13.16%	in H ₂ O, dried at 100C 2 hrs.
Purolite C-150	1.65eq/L	1.9eq/L	13.16%	in MeOH, dried at room temp for 2 days.
AG 50W X-2	4.16meq/g	5.2meq/g	20.00%	in H ₂ O, dried at 110C 6 hrs.
AG 50W X-2	4.15meq/g	5.2meq/g	20.19%	in MeOH, dried at 110C 6 hrs.
AG 50W X-2	4.35meq/g	5.2meq/g	16.35%	in H ₂ O, dried as above, treated with 0.5M HCl
AG 50W X-2	4.6meq/g	5.2meq/g	11.54%	in MeOH, dried as above, treated with 0.5M HCl
Nafion 511	0.89meq/g	0.9meq/g	0.11%	in H ₂ O, dried at 110C 2 hrs.
DOW FSA	1.19meq/g	-----	-----	in MeOH, dried at 110C 2 hrs.

F. Catalytic Synthesis of MTBE From Isobutene and Methanol Over Purolite C-150

Prior to this research, the Purolite resins had not previously been tested for the coupling of alcohols to form ethers and for the reaction of isobutene with methanol to form MTBE. Therefore, a screening test of the reaction of isobutene with methanol in a 316 stainless steel continuous downflow reactor was carried out prior to the more systematic testing that was described in an earlier section of this report. As before, the gas phase products were analyzed by gas chromatography using a Hewlett-Packard 5890 Series II GC with an in-line automated heated Valco sampling valve. The GC is interfaced with a H-P 3396 Series II recorder/integrator and a Gateway 2000 PC data station utilizing Chrom Perfect 2 software. Separations were achieved by means of a Chrompak Cp-Sil-5 capillary WCOT column (25 m x 0.32 mm I.D.) with a chemically bonded 5.0 micron methyl silicon coating.

The macroporous Purolite C-150 resin was first placed on a filter paper and acid-treated with 500 ml of 1 M HCl, and it was then air dried in an oven at 80°C over a weekend. After weighing 0.2559 g of the resin, it was mixed with ≈ 7 ml Pyrex beads and centered in the reactor by means of additional Pyrex beads and small plugs of Pyrex wool immediately above and below the diluted catalyst bed. The carrier gas consisted of N₂/He, and the flow rates of reactants and carrier gas were identical to those used by Baba et al. (3) with Amberlyst-15 resin, which gave a total flow rate of 0.5 mol/hr consisting of N₂/He:isobutene:methanol = 2:1:1. The carrier gas and isobutene flows were controlled by mass flowmeters, while the methanol was injected as a liquid above the reactor preheater section by means of a Gilson high pressure pump.

FIGURE 15

Catalytic testing was carried out at 65°C for 3 hr and at 75°C for 25 hr at ambient pressure. An experimental chromatogram, uncorrected for TCD sensitivity factors, obtained during the 75°C test is shown in Figure 15, and this shows that the coupling reaction was 100% selective to MTBE, with no dimethylether nor C₈ olefins being observed. With reactant flow rates of 488.5 mol methanol/kg cat/hr, 486.2 mol isobutene/kg cat/hr, and 975.3 mol (N₂/He)/kg cat/hr (total GHSV = 47,600 l/kg cat/hr), ≈16% of the methanol was converted to MTBE at 75°C, and this corresponds to a space time yield of ≈80 mol MTBE/kg cat/hr (≈7 kg MTBE/kg cat/hr). For comparison, Baba et al. (3) observed 11% conversion of isobutene to MTBE over Amberlyst-15 with 100% selective at 50°C.

REFERENCES

1. W.A. Dietz, *J. Gas Chromatogr.*, 5, 68 (1967).
2. K. Klier, R.G. Herman, R. Bastian, and S. DeTavernier, *DOE Technical Progress Report*, DOE/PC/90044-2, April 1991.
3. T. Baba, Y. Ono, T. Ishimoto, S. Moritaka, and S. Tanooka, *Bull. Chem. Soc. Jpn.*, 58, 2155 - 2156 (1985).
4. K. Dorfner, "Ion Exchangers" (Ed. by K. Dorfner) Walter de Gruyter: Berlin, 22 (1990).
5. E.M. Arnett, R.A. Haaksma, B. Chawla, and M.H. Healey; *J. Am. Chem. Soc.*, 108, 4888 (1986).
6. K. Tanabe, M. Misano, Y. Ono, and H. Hattori, "New Solid Acids and Bases," Elsevier: Amsterdam, 175 (1989).
7. J.G. Nunan, K. Klier, and R.G. Herman, *J. Chem. Soc., Chem. Comm.*, 676 (1985).
8. H. Knözinger, *Angew. Chem. Intern. Ed.* 7, 791 (1968).
9. H. Pines and J. Manassen, *Advan. Catal.*, 16, 49 (1966).

END

DATE
FILMED

2/11/92

I