NOV 02 1992

FUNDAMENTAL MECHANISMS IN FLUE GAS CONDITIONING

QUARTERLY REPORT
July 1992 - September 1992

DOE/PC/90365--T8

DE93 006435

SRI-ENV-92-870-7375-Q5

Contract No. DE-AC22-91PC90365

October 27, 1992

Todd R. Snyder
P. Vann Bush

SOUTHERN RESEARCH INSTITUTE
2000 NINTH AVENUE SOUTH
P.O. Box 55305
BIRMINGHAM, ALABAMA 35255-5305

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Prepared for

Felixa Eskey, Project Manager
UNITED STATES DEPARTMENT OF ENERGY
Pittsburgh Energy Technology Center
Post Office Box 10940, MS 922-206
Pittsburgh, Pennsylvania 15236-0940

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>PAGE</u>
INTRODUCTION.....	1
SUMMARY	1
TASK 2: ANALYSES OF MIXTURES OF SORBENTS AND ASHES	2
E 2.1 Standard Characterization of Mixtures of Sorbents and Ashes	2
E 2.2 Characterization of Water Adsorption by Mixtures of Sorbents and Ashes ..	11
E 2.3 Characterization of Water-Conditioned Sorbent and Ash Mixtures	13
TASK 3: ANALYSES OF ASHES AND POWDERS	15
E 3.1 Standard Characterization of Powders and Fly Ashes	15
E 3.2 Characterization of Water Adsorption by Powders and Fly Ashes	22
E 3.3 Characterization of Water-Conditioned Powders and Fly Ashes.....	24
E 3.4 Solvent Leaching Studies of Fly Ashes	27
Scholz.....	29
Monticello.....	31
Harrington	32
AFBC.....	33
Effects of Leaching on Ash Resistivity	34
PLANS FOR THE UPCOMING QUARTER.....	46

the SRI-EPA resistivity prediction model showed that the model could not accurately predict the resistivities we measured for leached and unleached dust cake ashes.

TASK 2: ANALYSES OF MIXTURES OF SORBENTS AND ASHES

E 2.1 Standard Characterization of Mixtures of Sorbents and Ashes

During the past quarter, we obtained samples of base line ash and particulate product of a conventional spray dryer application from Plant Kintigh in Somerset, NY, and the EPRI High Sulfur Test Center (HSTC) at this plant. SEM pictures of these two samples are shown in Figures 1 and 2. Effects of sorbent addition on particle morphology are evident in photographs of the spray dryer ash (Figure 2) by the presence of irregularly-shaped sorbent particles and deposits on the surfaces of spherical fly ash particles. In contrast, base line ash particles (Figure 1) are relatively smooth spheres typical of pulverized-coal (PC) fly ashes.

Size distributions of Muskingum and Plant Kintigh base line ashes, and mixtures of ashes and sorbents collected from the DOE Duct Injection Test Facility (DITF) at the Muskingum Plant, and from the baghouse downstream of the HSTC spray dryer at Plant Kintigh are presented in Figures 3 through 8. The mass median diameters (MMDs) of these distributions as measured in a centrifugally-augmented sedigraph are presented in Table 1. They are listed by sample identification (SID) number.

Table 1
Summary of Size Distribution Data for Task 2 Samples

SID	Description/Source	Stokes' MMD, μm
2870	Muskingum base line ESP hopper ash	14
2871	dry injection of $\text{Ca}(\text{OH})_2$ coplanar with water spray; (DITF)	6.7
2872	injection of $\text{Ca}(\text{OH})_2$ slurry; (DITF)	6.9
2873	injection of $\text{Ca}(\text{OH})_2$ slurry with CaCl_2 additive; (DITF)	5.7
2884	Kintigh base line ESP hopper ash	22
2885	conventional spray dryer; (High Sulfur Test Center)	9.8

a

b

c

d

Figure 1. SEM photographs of Plant Kintigh base line ESP hopper ash (SID 2884) taken at magnifications of a) 100X, b) 500X, c) 1000X, and d) 5000X.

a

b

c

d

Figure 2. SEM photographs of the sorbent and ash mixture produced in the conventional spray dryer located at the High Sulfur Test Center (SID 2885) taken at magnifications of a) 100X, b) 500X, c) 1000X, and d) 5000X.

Figure 3. Size distribution of Muskingum base line ESP hopper ash (SID 2870). P_m is the fraction of mass in the given size band.

Figure 4. Size distribution of the sorbent and ash mixture from tests of dry $\text{Ca}(\text{OH})_2$ injection at the DITF (SID 2871). P_m is the fraction of mass in the given size band.

Figure 5. Size distribution of the sorbent and ash mixture from tests of $\text{Ca}(\text{OH})_2$ slurry injection at the DITF (SID 2872). P_m is the fraction of mass in the given size band.

Figure 6. Size distribution of the sorbent and ash mixture from tests of $\text{Ca}(\text{OH})_2$ slurry injection with CaCl_2 addition at the DITF (SID 2873). P_m is the fraction of mass in the given size band.

Figure 7. Size distribution of Plant Kintigh base line ESP hopper ash (SID 2884). P_m is the fraction of mass in the given size band.

Figure 8. Size distribution of the sorbent and ash mixture produced in the conventional spray dryer located at the High Sulfur Test Center (SID 2885). P_m is the fraction of mass in the given size band.

In addition to size distributions, we also measured specific surface areas and true particle densities for Kintigh base line ash and HSTC spray dryer ash (Table 2). These data show the dramatic increase in specific surface area due to sorbent addition. (Data describing various characteristics of these samples following water conditioning are presented later in this report.)

Table 2
Additional Characterisitics of Plant Kintigh and HSTC Samples

SID	Description/Source	Specific Surface Area, m ² /g	True Particle Density, g/cm ³
2884	Kintigh base line ESP hopper ash	1.1	2.47
2885	conventional spray dryer; (HSTC)	10.7	2.53

E 2.2 Characterization of Water Adsorption by Mixtures of Sorbents and Ashes

Under Task 2, Experiment 2.2 we performed measurements of water content on ashes from Muskingum Station, the DITF, Plant Kintigh, and the HSTC. Prior to these determinations of water content, we conditioned weighed samples in sealed environments with controlled levels of relative humidity. This condition does not necessarily imitate the exposure the ash would have in a flue gas stream; however, the intent of the experiment was to quantify differences in adsorption of water among the ashes so that we could learn what properties of ashes govern adsorption mechanisms. Table 3 presents results of Karl Fischer determinations of water content. We heated each sample to different temperatures in the oven, which serves as the extraction chamber of the Karl Fischer device, to determine relative strengths with which water was bound to the particles.

Table 3
Total Water Removed from Task 2 Samples During Karl Fischer Titration, % wt.

Relative Humidity, %		~ 50		~ 75		
Oven Temperature, °C:		150	300	60	150	300
SID	Description/Source	Water Extracted, % wt.				
2870	Muskingum ESP hopper ash	*0.36	*0.59	0.23	0.41	0.35
2871	DITF dry Ca(OH) ₂ injection	*1.4	*2.2	> 1.2	1.1	2.0
2872	DITF Ca(OH) ₂ slurry injection	*1.6	*3.2	*1.2	> 2.2	> 2.9
2873	DITF Ca(OH) ₂ + CaCl ₂ injection	*2.0	*3.3	*1.4	0.90	> 3.6
2884	Kintigh ESP hopper ash	*0.63	*0.42		0.44	0.61
2885	HSTC spray dryer ash	*2.0	> 3.5		1.9	> 4.5

* Time-resolved data not recorded; value expresses total water removed after 30 minute extraction. Total water that would eventually be removed with a longer extraction time may exceed this value.

These data contain some anomalies. For each sample, we expected that total water removed would increase with higher levels of relative humidity used for conditioning, and with higher oven temperatures in the Karl Fischer device. Deviations from these two expected trends occurred for all the samples in Table 3. When some of these anomalies were first observed, we began to record the cumulative amount of water measured in the Karl Fischer device as a function of time the sample was in the oven. Therefore, for some of these data, it may be that the 30 minute extraction time we used for these samples was not always sufficient to reach equilibrium. When time-resolved data showed that water was still being removed from the sample at the end of the 30 minute-extraction time, we have placed a > sign in front of the value reported in Table 3.

Figure 9 shows data we accumulated during titration of three of the samples listed in Table 3. The figure shows that, although we had not extracted all the water that was on two of the samples, significant differences among the samples can be distinguished. In the cases shown, we see the effects of particulate morphology and chemistry on adsorption of water. Dry and slurry-derived Ca(OH)₂ have very similar size distributions (mass median diameters of 6.7 and 6.9 μm, respectively). The slurry-derived sample has 44% higher specific surface area than the dry sample (7.5 vs. 5.2 m²/g). The material with higher surface area adsorbed more water. The effect of chemistry overrides the differences in morphology in the case of sorbent spiked with about 3.2% by weight of CaCl₂. Specific surface area of the spiked sorbent was

Figure 9. Total water reacted in the Karl Fischer Device as a function of reaction time for three mixtures of sorbent and ash from the DITF. After conditioning at a relative humidity of 75 %, these samples were baked in the Karl Fischer oven at 300 °C.

only 80% of plain $\text{Ca}(\text{OH})_2$ slurry (6.0 vs. 7.5 m^2/g). Even so, spiked sorbent adsorbed more water than plain slurry. This is attributed to the deliquescence of the CaCl_2 additive.

E 2.3 Characterization of Water-Conditioned Sorbent and Ash Mixtures

Uncompacted bulk porosity and tensile strength determinations were performed on samples that had been conditioned at a variety of relative humidities. Results of these measurements are included in Tables 4 and 5.

Table 4
Uncompacted Bulk Porosities of Selected Ashes
from Task 2 Studies as a Function of Relative Humidity

Relative Humidity, %:		~ 7	~ 27	~ 93
SID	Description/Source	Bulk Porosity, %		
2870	Muskingum ESP hopper ash	61	61	
2871	DITF dry $\text{Ca}(\text{OH})_2$ injection	87	87	
2872	DITF $\text{Ca}(\text{OH})_2$ slurry injection	88	87	
2873	DITF $\text{Ca}(\text{OH})_2$ + CaCl_2 injection	87	87	
2884	Kintigh ESP hopper ash			71

Table 5
Tensile Strength of Selected Ashes and Powders, Nt/m^2

Relative Humidity, %		~ 1	~ 50
SID	Description/Source	Tensile Strength, Nt/m^2	
2870	Muskingum ESP hopper ash		1.6
2871	DITF dry $\text{Ca}(\text{OH})_2$ injection		3.7
2872	DITF $\text{Ca}(\text{OH})_2$ slurry injection		> 9.5
2873	DITF $\text{Ca}(\text{OH})_2$ + CaCl_2 injection		> 6.8
2884	Kintigh ESP hopper ash		0.6
2885	HSTC spray dryer ash	> 30	4.2

Porosities of the DITF samples are significantly higher than the source Muskingum ash under the conditions tested so far (7 and 27% RH). Tensile strengths measured at 50% RH show that the sorbent mixtures are more cohesive than the base line fly ashes. Also, drying the spray dryer ash increases tensile strength dramatically. Further tests are planned and must be completed before any conclusions can be drawn about the role of relative humidity on the cohesivity of these samples. We hope to find relationships among adsorbed water content, bulk porosity, and tensile strength.

TASK 3: ANALYSES OF ASHES AND POWDERS

Task 3 studies involve analyses of a variety of powders, and leached and unleached dust cake ashes. In most of the discussions contained under Task 3, results of analyses performed on unleached dust cake ashes are being compared directly with similar analyses of leached dust cake ash samples. A detailed discussion of effects of leaching can be found in section E 3.4 which describes our solvent leaching studies. However, for convenience, we have included much of the data describing the characteristics and behavior of leached dust cake ashes in tables which can be found in sections E 3.1, E 3.2, and E 3.3.

E 3.1 Standard Characterization of Powders and Fly Ashes

Size distributions of Harrington dust cake ash (SID 2515), glass beads (SID 1856), and alumina powder (SID 2874) used in Task 3 are presented in Figures 10 through 12. MMD's of these distributions are included in Table 6, along with MMD values previously determined for other ashes and powders used in Task 3 analyses. (Because of their small particle size, no size distribution measurements were attempted on the three Cabosil silicon dioxide powders [SID's 3063, 3064, and 3065]. SEM photographs of glass beads, the three Cabosil silicon dioxide powders, and alumina powder are shown in Figures 13 through 15.

Figure 10. Size distribution of Harrington dust cake ash (SID 2515). P_m is the fraction of mass in the given size band.

Figure 11. Size distribution of glass beads (SID 1856). P_m is the fraction of mass in the given size band.

Figure 12. Size distribution of alumina powder (SID 2874). P_m is the fraction of mass in the given size band.

a

b

c

d

Figure 13. SEM photographs of glass beads (SID 1856) taken at magnifications of a) 100X, b) 500X, c) 1000X, and d) 5000X.

(a)

(b)

(c)

Figure 14. SEM photographs of a) Cabosil L-90 (SID 3063), b) Cabosil M-5 (SID 3064), and c) Cabosil EH-5 (SID 3065) taken at a magnification of 5000X.

6666-16

a

b

c

d

Figure 15. SEM photographs of alumina powder (SID 2874) taken at magnifications of a) 100X, b) 500X, c) 1000X, and d) 5000X.

Table 6
Summary of Size Distribution Data for Task 3 Samples

SID	Description/Source	Stokes' MMD, μm
2029	Monticello dust cake ash	4.6
2101	Scholz dust cake ash	8.9
1994	TVA 20 MW AFBC dust cake ash	2.7
2515	Harrington dust cake ash	5.7
1856	glass beads	24
3238	aluminosilicate (Neutralite)	13
2769	silicon dioxide (Kenite 900)	13
2874	alumina powder	36

We determined ash resistivity at three different moisture levels on four unleached dustcake ashes. These data are discussed and presented along with similar measurements performed on leached dust cake ashes under section E 3.4 Solvent Leaching Studies of Fly Ashes, later in this report.

E 3.2 Characterization of Water Adsorption by Powders and Fly Ashes

As in Experiment 2.2, we performed measurements of water content on powders and dust cake ashes using Karl Fischer titration. Prior to these determinations of water content, we conditioned weighed samples in sealed environments with controlled levels of relative humidity. Table 7 presents results of these Karl Fischer determinations of water content. We heated each sample to different temperatures to determine relative strengths with which water was bound to ash or powder particles.

Table 7

Total Water Removed from Task 3 Samples During Karl Fischer Titration, % wt.

Relative Humidity, %		~ 50			~ 75		
Oven Temperature, °C:		60	150	300	60	150	300
SID	Description/Source	Water Extracted, % wt.					
2101	Scholz dust cake ash	*0.80	> 2.0	> 2.5		*2.0	*2.7
2029	Monticello dust cake ash	0.078	> 0.24	*0.39		*0.15	> 0.40
2515	Harrington dust cake ash	0.011	> 0.35	*0.85	*0.29	0.29	0.27
1994	AFBC dust cake ash	1.2	2.0	*2.4	2.2	1.9	2.7
2101-W	leached Scholz dust cake ash	0.52	*0.67	*1.2	0.56	0.68	> 1.4
2029-W	leached Monticello dust cake ash	0.07	*0.14	*0.20	0.14	0.19	0.33
2515-W	leached Harrington dust cake ash	> 1.3	*1.9	*2.6	> 1.7	> 2.7	3.9
1994-W	leached AFBC dust cake ash	> 2.7	*4.2	*4.8		> 3.8	4.2
1856	glass beads	0.00	*0.20	*0.20		0.19	0.22
3063	silicon dioxide (Cabosil L-90)		*0.49	*0.63	0.61	0.63	1.4
3238	aluminosilicate (Neutralite)		*0.65	*2.7		> 2.3	2.0
2769	silicon dioxide (Kenite 900)		*0.12	*0.20	0.11	0.099	0.41
2874	alumina powder		*0.08	*0.10	0.025	0.061	0.16

* Time-resolved data not recorded; value expresses total water removed after 30 minute extraction. Total water that would eventually be removed with a longer extraction time may exceed this value.

Most of these data show expected increases in the quantity of extracted water due to increasing the oven temperature and increasing the relative humidity at which the samples were conditioned. Exceptions to this are sample 2515, Harrington dust cake ash, and sample 3238, aluminosilicate powder. We do not have explanations for these exceptions and therefore plan to do further testing to elucidate these cases.

Powders were tested to help us refine our techniques for discriminating the effects of particulate chemistry and morphology. Two silicon dioxide powders with distinct particle size and surface areas were tested. Sample 3063 is a fumed silica product (98% silica) with a specific surface area of 100 m²/g. Sample 2769 is diatomaceous earth (91% silica) with a specific surface area of 1.4 m²/g. Karl Fischer data show that over three times the water could be extracted from the higher surface area material as from the low surface area material.

Aluminosilicate powder (75% alumina and 13% silica) has a specific surface area of 1.4 m²/g, the same value as diatomaceous earth. Aluminosilicate powder and diatomaceous earth also have the same mass median diameter. Aluminosilicate powder adsorbed much more water than silica. This result is in accord with the hydrophobic character of silica, and is clear evidence of the importance of particulate chemistry in adsorption.

Ash samples conditioned at 50% and 75% RH gave predicted results from Karl Fischer titrations. Scholz ash is known to have excess, unreacted sulfuric acid on the surfaces of the particles. High affinity of acid to water is probably the cause of the adsorption of relatively large amounts of water on Scholz ash particles. AFBC particles consist of significant amounts of calcium sulfite or sulfate (18% soluble sulfate content), with an affinity for water. High surface area and the chemical makeup of AFBC ash result in adsorption of large amounts of water. Monticello and Harrington ashes have low specific surface areas, and high alkali contents. Both of these ashes adsorbed about the same amount of water, and much less than Scholz or AFBC ashes. We will continue detailed analyses of the adsorption data to determine the controlling mechanisms.

E 3 3 Characterization of Water-Conditioned Powders and Fly Ashes

Uncompacted bulk porosities of ashes and powders that were conditioned and tested at a variety of relative humidities are summarized in Table 8. Figure 16 presents a graph of these data for eight dust cake ashes. For Scholz, Monticello, and Harrington dust cake ashes, water conditioning increased ash cohesivity as measured by bulk porosity, although, except for unleached Scholz ash, relatively high humidities were required to significantly increase cohesivity. Because of sulfate salts and free sulfuric acid on the surfaces of the particles, unleached Scholz ash readily adsorbed water. We believe that porosity of AFBC ash stayed relatively constant because all water adsorbed onto the surfaces of the ash particles was subsequently absorbed into the particles. We discuss these data further under section 3.4.

Figure 16. Uncompacted bulk porosity of leached and unleached dust cake ashes as a function of the relative humidity used to condition the ashes.

Table 8
Uncompacted Bulk Porosities of Powders and Dust Cake Ashes
as a Function of Relative Humidity

Relative Humidity, %:		~ 7	~ 27	~ 53	~ 75	~ 93
SID	Description/Source	Bulk Porosity, %				
2101	Scholz dust cake ash	77	76	78	82	87
2029	Monticello dust cake ash	64	67	68	69	80
2515	Harrington dust cake ash	74	76	75	76	78
1994	AFBC dust cake ash	90	88	90	89	91
2101-W	leached Scholz dust cake ash	73	72	72	72	80
2029-W	leached Monticello dust cake ash	65	63	64	64	80
2515-W	leached Harrington dust cake ash	77	74	76	76	80
1994-W	leached AFBC dust cake ash	90	89	91	90	91
3238	aluminosilicate (Neutralite)					95
2769	silicon dioxide (Kenite 900)					92
2874	alumina powder					81

We performed tensile strength determinations on most of the powders and ashes that we currently have on hand. We made these measurements on samples that had been conditioned at a variety of relative humidities. Results of these measurements are included in Table 9. Apparent increases in tensile strength of samples conditioned and tested at very low relative humidities were unexpected. We have planned more tests to verify this trend. We will also try to determine if static charge on the ash particles may be leading to the measurement of high tensile strengths for very dry samples.

Table 9
Tensile Strength of Dust Cake Ashes and Powders, Nt/m²

Relative Humidity, %		~ 1	~ 50	~ 75
SID	Description/Source	Tensile Strength, Nt/m ²		
2101	Scholz dust cake ash	11	5.1	5.4
2029	Monticello dust cake ash		8.2	8.5
2515	Harrington dust cake ash		15	
1994	AFBC dust cake ash		> 7.7	
2101-W	leached Scholz dust cake ash	15	2.8	
2029-W	leached Monticello dust cake ash	> 30	3.2	3.6
2515-W	leached Harrington dust cake ash		1.6	
1994-W	leached AFBC dust cake ash		> 9.5	
1856	glass beads	7.9	0.8	
3238	aluminosilicate (Neutralite)		1.4	
2769	silicon dioxide (Kenite 900)		> 4.4	
2874	alumina powder	3.3	0.8	

Monticello ash has about twice the silica content of Harrington ash. The fact that Monticello ash has a low cohesivity is well known. Harrington ash had about twice the tensile strength of Monticello ash when both were conditioned at 50% RH. This difference in tensile strength could result from differences in silica content that affect the formation of liquid bridges. Additional discussions of these tensile strength data are included below.

E 3.4 Solvent Leaching Studies of Fly Ashes

During the past quarter, additional analyses were performed on leached dust cake ashes described in our most recent quarterly report (April - June 1992). Since we present a lengthy discussion of the effects of solvent leaching on ash properties in this report, we have also included a description of the method used to leach soluble compounds from the four dust cake ashes. Leaching tests were performed in two experiments. We designed our first experiment to determine if we could remove significant amounts of soluble compounds from the surfaces of dust cake ash particles by exposing the ash particles to an excess of water. Leachate samples were produced by sequentially passing 10 ml samples of distilled, deionized water through a 5 gram sample bed of dust cake ash. A slight vacuum (17 to 20 in H₂O) was used

to pull the water and dissolved solids through a fritted glass filter (4-8 μm pore size) for collection. Additional distilled, deionized water was used to wash the walls of the collection vessel. Total collected leachate and wall washings were then diluted up to 25 ml total volume. This process was repeated ten times for each dust cake ash. Leachate samples were then submitted for chemical analyses. Results of these analyses, which demonstrated that significant quantities of several soluble compounds were removed from particle surfaces during leaching, were presented in our last quarterly report. To determine the effects removal of soluble compounds would have on ash behavior, we performed a second leaching experiment. In this second experiment, 50 g samples of each of the dust cake ashes were leached using the same procedure and the same ratio of ash to distilled, deionized water as in our first experiment. We generated samples of leached dust cake ashes identified as 2101-W, 2029-W, 2515-W and 1994-W in our second experiment and used them in a variety of subsequent analyses.

We performed chemical analyses on leached dust cake ashes from Scholz, Monticello, Harrington and TVA's pilot-scale AFBC (2101-W, 2029-W, 2515-W, and 1994-W). Results of these analyses are presented in Table 10 along with results obtained earlier for unleached ash samples (2101, 2029, 2515, and 1994). (Soluble $\text{SO}_4^{=}$ data presented in Table 10 have been corrected; some $\text{SO}_4^{=}$ values previously reported were incorrect because of errors in analysis and reporting.)

Table 10
Chemical Characteristics of Dust Cake Ashes, % wt.*

Source	Scholz		Monticello		Harrington		AFBC	
SID	2101	2101-W	2029	2029-W	2515	2515-W	1994	1994-W
LiO ₂	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
Na ₂ O	0.82	0.62	0.45	0.52	1.3	1.2	0.35	0.39
K ₂ O	3.3	2.7	0.98	0.96	0.34	0.31	1.4	1.5
MgO	0.99	0.97	2.3	2.4	6.2	6.2	0.81	0.93
CaO	3.4	1.7	10.2	9.6	29.3	27.9	29.7	26.2
Fe ₂ O ₃	19.9	19.9	3.5	3.2	5.5	5.3	14.4	13.9
Al ₂ O ₃	19.2	19.7	20.3	20.3	18.8	18.7	11.0	12.6
SiO ₂	50.1	49.9	60.4	60.4	31.7	33.7	23.6	26.5
TiO ₂	1.0	1.1	1.6	1.3	1.3	1.2	0.54	0.58
P ₂ O ₅	0.21	0.24	0.08	0.16	1.4	1.5	0.14	0.19
SO ₃	1.00	0.13	0.53	0.08	2.5	1.5	17.4	15.4
LOI	11.8	8.0	0.37	0.65	0.24	6.1	12.7	18.6
soluble SO ₄ ⁼	3.8	0.32	0.52	0.13	3.0	2.5	18.4	15.1
Equilibrium pH	4.8	5.7	9.9	8.7	11.2	10.7	11.5	10.2

* Equilibrium pH is a dimensionless quantity

All four ashes lost some calcium, SO₃, and soluble sulfate when leached. In every case pH became closer to neutral. For all but the AFBC ash specific surface area after leaching was greater; surface area of the AFBC ash decreased by 12 %.

Scholz

Scholz ash had the largest reduction in Ca, losing 50% of calcium when leached. This loss was especially significant since unleached Scholz ash has the lowest concentration of Ca among the ashes we tested. Furthermore, the concentration of alkali metals was lower in leached Scholz ash; Na dropped 24%, K 18%, and Mg 2%.

Scholz ash has a high concentration of Fe, some of which was evidently easily removed by leaching (5 ppm Fe was found in the first leachate of the series of 10 leachates and none

detected in subsequent leachates). However, there was no difference in iron contents of leached and unleached ashes.

Sulfur content that we determined as SO_3 was reduced by leaching from 1% to 0.13% of the mass of the ash. Sulfur that we determined as soluble sulfate was reduced from 3.8 to 0.32% by weight. (There is some uncertainty about the soluble sulfate levels, since the leachate of Scholz ash suggested soluble sulfate amounts equivalent to 4.5% of the weight of the ash, more than what was measured in the ash.) Reduction in sulfur was about three times more on a weight basis than the reduction in alkali. This result suggests that free sulfuric acid and sulfate salts were removed by leaching. Predictably, the effect of the leaching was a decrease in acidity (pH increased from 4.8 to 5.7).

Specific surface area of Scholz ash increased from $3.0 \text{ m}^2/\text{g}$ to $8.3 \text{ m}^2/\text{g}$ as a result of leaching. In spite of the increase in surface area, leached Scholz ash adsorbed about half as much water as unleached ash. This result was possibly related to the leaching of acid from the surface, though the increase in surface area may be caused by changes to features of particles that would not affect adsorption because of their size or location. Nevertheless, in the case of Scholz ash, it seems that surface chemistry governs adsorption and retention of water more than does surface morphology.

Leached Scholz ash had lower values of uncompact bulk porosity than unleached ash except when conditioned at relative humidities above 90%. Leached ash showed no effect of relative humidity (RH) on porosity at levels of 7, 28, 53, and 75% RH. Unleached ash showed a relative steady increase in bulk porosity as RH was increased from 26 to 53 to 75 to 92%. Bulk porosity of leached ash increased sharply (from 72 to 92%) after conditioning at 94% RH. These results are plausibly related to the lower affinity for water of leached ash, as evidenced by Karl Fischer measurements of samples conditioned at 50 and 75% RH.

At 50% RH the tensile strength of leached ash was 45% *lower* than the tensile strength of unleached ash. At 1% RH the tensile strength of unleached ash was 36% *higher* than the tensile strength of unleached ash. Furthermore, the tensile strengths of both ashes were significantly *greater* at the low RH of 1% than at 50% RH. These are three surprising results. First, we intuitively expected the higher specific surface area of leached ash at 50% RH to correlate with higher tensile strength. Lower tensile strength of leached ash does correspond with lower adsorbed water. Second, we expected the tensile strengths of desiccated samples to change in some proportion to adsorbed water on the samples, but unleached ash had more

water content at 50% RH and had a smaller change in tensile strength than leached ash. Third, we expected the desiccated samples to have lower tensile strengths than samples conditioned at 50% RH because of reduced liquid bridging and capillary forces of adhesion. Evidently, a more complex mechanism is involved in particle-to-particle adhesion. We suspect that changes in van der Waals forces caused by changes in materials at contact points or closeness of contact points are involved in these results, as may be the strengths of ionic bonds. We cannot rule out the electrostatic effects at very low humidities, either.

Monticello

Monticello ash had the least reduction in alkali of the four ashes leached. Ca content of leached ash was 6% less by weight than unleached ash (9.6 vs. 10.2%) and the K was 2% less, but Na was 16% more (from 0.45 to 0.52% wt) and Mg was 4% more. Overall, the content of these four alkali metals was reduced a little more than 3% by leaching the ash. Fe content was reduced from 3.5 to 3.2% of the weight.

Sulfur content of Monticello ash was reduced by about 80% by leaching. Sulfur we measured as SO_3 went from 0.53 to 0.08% of the weight of the ash. The content of soluble sulfate was reduced from 0.50 to 0.13% of the weight. The net effect of leaching on pH was a decrease from 9.9 to 8.7.

Specific surface area of the Monticello ash increased from 0.98 to 1.6 m^2/g as a result of the leaching. Data on water content of samples of ash conditioned at 50% and 75% RH did not give consistent results. Water content of the leached sample was lower than that of the unleached sample at 50% RH, and higher at 75% RH. Percent of weight of ash lost on ignition at 750 °C increased from 0.37 to 0.65 after leaching, suggesting more water was contained in the ash after it had been leached. The inconsistency in water content prevents us from simply interpreting the relative roles of morphology and surface chemistry in adsorption of water by Monticello ash.

The effect of the leaching on bulk porosity was virtually the same as the effect on Scholz ash: leached ash had slightly lower porosity and showed less sensitivity to RH below 90% than unleached ash. Bulk porosity of unleached ash gradually increased as RH was increased over the range from 6 to 75%. As with Scholz ash, leached Monticello ash had a significantly lower tensile strength than unleached ash. Lower tensile strength and lower porosity are compatible results since it is presumably weaker adhesive forces between particles that allow

the particles to pack in less open (less porous) arrangements. Again, reduced interparticle adhesion manifested by lower tensile strength and porosity occurred together with increased specific surface area.

Harrington

Leaching Harrington ash removed only slightly more alkali metals than leaching Monticello ash. Small decreases in Na and K content were probably within the margin of error of the measurements, and Mg content was unchanged. Ca content changed on a percentage basis less than any of the ashes, dropping from 29.3 to 27.9% of the weight of the ash.

Sulfur content of the Harrington ash was reduced by about 27% by leaching. Sulfur measured as SO_3 went from 2.5 to 1.5% of the weight of the ash. Soluble sulfate dropped from 3.3 to 2.5 % of the weight of the ash. pH of the Harrington ash decreased from 11.2 to 10.7 as a result of leaching.

The percentage of weight evolved on ignition at 750 °C increased from 0.24 for unleached ash to 6.1 for leached ash. Evidently, water used to leach Harrington ash reacted with Ca in the ash to form hydrates, hemihydrates, or other compounds, binding the water so that only part of it was removed by baking at 150 °C. Results of Karl Fischer measurements showed that amounts of water extracted at 150 °C were very different for leached and unleached samples. After exposing the ashes to air with 50% RH, leached Harrington ash had over five times the water content of unleached ash. After exposing the ashes to air with 75% RH, leached ash had more than 20 times the water content of unleached ash.

In this case, changes in particle morphology coincide with changes in water adsorption. Specific surface area of Harrington ash increased from 1.5 to 7.1 m^2/g after it was leached. This nearly 5-fold increase is not as large as the difference in water extracted from samples conditioned at 75% RH. (The relationship between surface area and water content was inverse for Scholz ash and mixed for Monticello ash). In fact, the high weight loss on ignition of leached Harrington ash and potential chemical affinity of water and high-calcium ash suggest chemistry is equally, if not more, important in determining adsorption of water.

Uncompacted bulk porosity of unleached Harrington ash showed no dependence on relative humidity over the range from 6 to 92%. There was no difference between the bulk porosities of leached and unleached ashes at 6, 27, 53, and 75% RH. But, at 92% RH porosity of

leached ash *decreased*. Furthermore, the tensile strength of leached ash conditioned at 50% RH was only one-tenth the tensile strength of unleached ash. These apparent reductions in interparticle adhesion are perhaps surprising since Karl Fischer and LOI data showed that adsorbed water content increased with increasing RH.

Summarizing the findings for Harrington ash, we note that leaching resulted in:

1. An increase in specific surface area by more than four-fold
2. An increase in adsorption of water by as much as twenty-fold
3. A decrease in tensile strength by almost ten-fold

These results indicate that surfaces of Harrington ash particles contain chemicals that are not only hydrophilic, but may chemically react with adsorbed water or sequester the water so that it is precluded from forming liquid bridges. It may also be possible that adsorbed water dissolves solid salt bridges between particles. We will have to do further studies with ashes and powders to identify the effective mechanism(s).

AFBC

AFBC particulate matter is a combination of fly ash and particles of CaCO_3 , CaSO_4 , or CaSO_3 from the fluidized bed. The Ca content of unleached material is 29.7%, which is almost exactly the same amount as is found in Harrington ash. Since Ca in AFBC particulate matter is in a different form than Harrington ash it is not surprising that results of leaching the two powders differed. AFBC particulate matter lost almost 12% of Ca content when leached. There was a commensurate increase in percent of weight of Si and Al for leached ash, indicating that the source of reduction in Ca was the limestone added to the boiler. Total alkali content of AFBC particulate matter decreased by only 10%: the Na, K, and Mg fractions of the weight of leached ash increased slightly.

AFBC material had a relatively high concentration of sulfur because of the reaction between the limestone and sulfur oxides in the combustor. Sulfur content was reduced by about 15% by leaching. Sulfur measured as SO_3 went from 17.4 to 15.4% of the weight of the samples, and soluble sulfate went from 18.4 to 15.1%. pH of the material became more neutral, decreasing from 11.5 to 10.2.

Specific surface area of AFBC material decreased from 20.9 to 18.4 m^2/g as a result of leaching. Leached AFBC particulate matter adsorbed about twice as much water as unleached material when exposed to air with 50% and 75% RH.

Leaching AFBC particulate matter had no significant effect on its uncompacted bulk porosity. Neither was there any effect of relative humidity on bulk porosity. This result was like that obtained with Harrington ash. We were unable to measure tensile strength of AFBC material at room conditions (50% RH).

Effects of Leaching on Ash Resistivity

We measured resistivity as a function of ash temperature for the leached dustcake ashes in descending temperature mode. These data and corresponding data taken for unleached dust cake ashes are shown in Figures 17 through 28. Amounts of adsorbed water and soluble compounds on the surfaces of ash particles are prime determinants of the degree of surface conduction. (Overall conduction of current through an ash layer combines surface conduction and volume conduction.) For all eight ashes tested, conditioning samples with increased levels of water vapor decreased the ash resistivity for temperatures below 200 to 300 °C. At temperatures above 300 °C, the amount of water that could be adsorbed onto surfaces of ash particles was apparently too low to promote surface conduction.

We believe that the unleached Monticello ash has a higher resistivity than unleached Harrington ash because of a difference in surface conduction. In our analyses of leachate samples, a much larger amount of soluble Na^+ was removed from Harrington ash during the leaching cycles than from Monticello ash. Na present on the surface of ash particles serves as a very effective, mobile charge carrier. After each of these two ashes had most of the Na (and SO_3 and $\text{SO}_4^{=}$) removed from their particle surfaces during leaching, their overall resistivities were increased, and became much more similar. Although Na was effectively removed from the surfaces of the Harrington ash particles during leaching, the total amount of Na present in the ash dropped only slightly. Therefore Na within particles was still available for promoting volume conduction at higher ash temperatures. A possible explanation of the apparent decrease in volume conduction of leached Harrington ash is given below.

One of the changes that occurred in Monticello and Harrington ashes during leaching was inclusion of significant quantities of water in the form of hydrates with alkaline metals (Na, K, Mg, and Ca). Presence of these metallic hydrates is evident in increased LOI values measured for these two leached ashes (Table 10). LOI nearly doubled for Monticello ash, and increased by a factor of twenty five for Harrington ash. Water contents of Harrington ashes measured with Karl Fischer titration also demonstrate about an order of magnitude increase in water

Figure 17. Leached and unleached Scholz dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a dry (0% water) environment.

Figure 18. Leached and unleached Scholz dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (10% water) environment.

Figure 19. Leached and unleached Scholz dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (18% water) environment.

Figure 20. Leached and unleached Monticello dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a dry (0% water) environment.

Figure 21. Leached and unleached Monticello dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (10% water) environment.

Figure 22. Leached and unleached Monticello dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (18% water) environment.

Figure 23. Leached and unleached Harrington dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a dry (0% water) environment.

Figure 24. Leached and unleached Harrington dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (10% water) environment.

Figure 25. Leached and unleached Harrington dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (18% water) environment.

Figure 26. Leached and unleached AFBC dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a dry (0% water) environment.

Figure 27. Leached and unleached AFBC dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (10% water) environment.

Figure 28. Leached and unleached AFBC dustcake ash resistivity as a function of temperature during descending-temperature resistivity determinations made in a moist (18% water) environment.

content of leached ash in comparison with unleached ash. We postulate that pozzolanic reactions occur, binding water with ash to form hydrocalcium silicates. This cement-like material is very stable. The apparent reduction in volume conductivity of Harrington ash caused by leaching can be attributed to formation of these hydrocalcium silicates. Calcium ions which are available for charge transfer in unleached ash form hydrogen bonds with water during leaching. This bonding may inhibit charge transfer that the calcium would otherwise be available for, thereby significantly decreasing volume conduction. We believe that, on a reduced scale, a similar process occurs with Monticello ash.

Leaching produced quite unexpected results for measured resistivities of Scholz ash. Although leaching removed Na^+ , SO_3 and $\text{SO}_4^{=}$ from particle surfaces, resistivity at the lower temperature range (where surface conduction is dominant) was *decreased* by about one order of magnitude. At higher temperatures reduction in resistivity was not as pronounced. Several factors may have influenced this behavior. Bickelhaupt has stated that resistivity can be expected to decrease when surface area increases because of increased water adsorption. Our data support this statement. Leaching increased specific surface area of Scholz ash from 3.0 to 8.3 m²/g. Decrease in the resistivity of leached Scholz ash was measured only when samples were conditioned and tested in moist environments, and finally, the difference in the resistivities of leached and unleached Scholz ashes became less significant as ash temperature increased. (However, an even larger increase in surface area, from 1.5 to 7.1 m²/g, for Harrington ash was accompanied by an *increase* in resistivity for moist and dry samples.) Another change in Scholz ash caused by leaching was the decrease in cohesivity of leached ash. A loosely packed bulk sample of leached Scholz ash would be less porous, and contain more contact points, than a similar sample of unleached Scholz ash. (Resistivity is measured for loosely packed samples of ash.) More contact points may promote better surface and volume conduction. A third possibility for increased surface conduction for leached Scholz ash is rearrangement and deposition of soluble salts on the particle surfaces and especially at contact points between particles. Although the leaching technique we used removed the vast majority of soluble compounds from the particle surfaces, enough salts may accumulate when the sample was being dried following the leaching procedure to build salt bridges between particles. If conductivity of this bridge was sufficiently high, electrical conduction between particles could be significantly enhanced. A crystalline salt was found in large quantities in the first few leachate samples from the leaching of Scholz ash. Because of its golden color and crystalline structure, we believe this salt to be $\text{Fe}_2(\text{SO}_4)_3$. If this compound were present in increased concentrations at contact points between particles in leached ash, or if some type of matrix of highly conductive salt were deposited in a film-like structure on the particles, surface

conduction might improve. At this time we are not able to say which, if any, of these mechanisms explain Scholz resistivity data.

The only increase in the resistivity of AFBC ash caused by leaching was for very dry ash at very low temperatures. AFBC resistivity data do tend to support the argument relating reduced volume conduction in leached Harrington ash to the presence of hydrocalcium silicates. Because of the high concentration of calcium in AFBC ash, similar pozzolanic reactions could occur with this ash. Resistivities of leached Harrington and leached AFBC ashes are very similar at all three moisture contents.

The resistivity prediction model that SRI developed for the EPA was run for leached and unleached dust cake ashes from Scholz, Monticello, and Harrington. Mineral analyses of the samples were used as the inputs to the model. Predicted relationships between temperature and resistivity in an environment containing 10 % water were compared with data measured for Scholz and Monticello ashes (Figures 29 and 30). These comparisons showed that the model does not accurately predict resistivity for these ashes. Predicted resistivity data for Harrington also differed significantly from measured values. These types of comparisons will continue throughout the remainder of this project.

PLANS FOR THE UPCOMING QUARTER

We will be continuing laboratory experiments under Task 3 on dust cake ashes and powders. Under Task 2, we will be performing a variety of analyses on ashes and mixtures of ashes and sorbents with emphasis on Karl Fischer titration, tensile strength measurements, resistivity measurements, and further uncompacted bulk porosity determinations.

Figure 29. Measured and predicted values of ash resistivity of leached and unleached Scholz dustcake ashes in a moist (10% water) environment.

Figure 30. Measured and predicted values of ash resistivity of leached and unleached Monticello dustcake ashes in a moist (10% water) environment.

FUNDAMENTAL MECHANISMS IN FLUE GAS CONDITIONING

QUARTERLY REPORT

July 1992 - September 1992

SRI-ENV-92-870-7375-Q5

Contract No. DE-AC22-91PC90365

October 27, 1992

Approved by

A handwritten signature in dark ink, appearing to read "Duane H. Pontius", is written over a solid horizontal line.

Duane H. Pontius Head, Particulate Science Division

END

**DATE
FILMED**

3 / 12 / 93