ANL--89/34

DE92 004050

ARGONNE NATIONAL LABORATORY
9700 South Cass Avenue
Argonne, Illinois 60439

ANL-89/34

**CHEMICAL ALTERATION OF LIMESTONE AND MARBLE SAMPLES EXPOSED TO ACID RAIN
AND WEATHERING IN THE EASTERN UNITED STATES, 1984-1988**

by

K. J. Reimann

Materials and Components Technology Division

Work completed September 1989
Published June 1991

Work Sponsored by

U.S. National Park Service, as part of the
National Acid Precipitation Assessment Program

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

CONTENTS

ABSTRACT	1
1 INTRODUCTION	1
2 SUMMARY OF EXPERIMENTAL PROCEDURES.....	3
3 RESULTS	6
4 DISCUSSION AND CONCLUSIONS.....	8
ACKNOWLEDGMENTS.....	29
REFERENCES.....	30
APPENDIX A: Stone Surface Sampling Procedure and Summary of Sampling and Analytical Report.....	31
APPENDIX B: Specifications of Field Procedures from Site Management Plan.....	33
APPENDIX C: Protocols for IC and ICP Analyses.....	37
APPENDIX D: Results of IC and ICP Analyses.....	43

FIGURES

1 Dimensions and Layer Designation of Briquette Specimens	3
2 Sulfate Distribution among Layers for the NC Site. Legend: + Quarterly; Δ Annual; □ Biennial; ▲ Triennial; ■ Quadrennial.....	9
3 Average Sulfate Concentration in the Topmost, Skyward, A, Layer of the (a) Marble and (b) Limestone Test Briquettes from the Five NAPAP Materials Exposure Sites after 0.25, 1, 2, 3, and 4 Yr of Exposure.....	10
4 Average Sulfate Concentration in the Outermost, Groundward Z, Layer of the (a) Marble and (b) Limestone Test Briquettes from the Five NAPAP Materials Exposure Sites after 0.25, 1, 2, 3, and 4 Yr of Exposure	11
5 Photographs of Groundward Surfaces of Limestone Test Briquettes After Exposed at the DC Site: after (a) 1 Quarter, (b) 1 Yr, and (c) 3 Yr.....	16

6 Sulfate concentration through total thickness of preexposed limestone	21
---	----

TABLES

1 Installation and Removal Dates of Previously Unexposed Limestone and Marble Briquettes at Various Field Exposure Sites for Stone Surface Wet Chemistry and Mineralogical Profiling.....	5
2 Summary of IC Analyses of Control Samples for Anions	6
3 Summary of IC Analyses of Limestone from the North Carolina Site for Anions, Quarterly, Annual, and Biennial Exposures.....	7
4 Summary of IC Analyses of Limestone from the North Carolina Site for Anions, Annual, and Multiyear Exposures	7
5 Summary of IC Analyses of Limestone from the New Jersey Site for Anions, Quarterly, Annual, and Biennial Exposures	12
6 Summary of IC Analyses of Limestone from the New York Site for Anions, Quarterly, Annual, and Multiyear Exposures	12
7 Summary of IC Analyses of Limestone from the New York Site for Anions, Annual and Multiyear Exposures.....	13
8 Summary of IC Analyses of Limestone from the Washington, DC, Site for Anions, Quarterly, Annual, and Biennial Exposures	14
9 Summary of IC Analyses of Limestone from the Washington, DC, Site for Anions, Annual and Multiyear Exposures.....	15
10 Summary of IC Analyses of Limestone from the Ohio Site for Anions, Quarterly, Annual, and Biennial Exposures	16
11 Summary of IC Analyses of Limestone from the Movable Rack at the Ohio Site for Anions, 1987-88.....	17
12 Summary of IC Analyses of Marble from the North Carolina Site for Anions, Quarterly, Annual, and Biennial Exposures	18
13 Summary of IC Analyses of Marble from the North Carolina Site for Anions, Annual and Multiyear Exposures.....	18
14 Summary of IC Analyses of Marble from the New Jersey Site for Anions, Quarterly, Annual, and Biennial Exposures	19

15	Summary of IC Analyses of Marble from the New York Site for Anions, Quarterly, Annual, and Biennial Exposures	19
16	Summary of IC Analyses of Marble from the New York Site for Anions, Annual and Multiyear Exposures	21
17	Summary of IC Analyses of Marble from the Washington, DC, Site for Anions, Quarterly, Annual, and Biennial Exposures	22
18	Summary of IC Analyses of Marble from the Washington, DC, Site for Anions, Third Annual, 1987-88; Triennial, 1984-87; and Quadrennial, 1984-88.....	23
19	Summary of IC Analyses of Marble from the Ohio Site for Anions, Quarterly, Annual, and Biennial Exposures.....	23
20	Summary of IC Analyses of Marble from the Movable Rack at Ohio Site for Anions, 1987-88	24
21	Summary of IC Analyses of Preexposed Stone Control Samples for Anions	25
22	Summary of ICP Analyses of Salem Limestone for Cations ^a	26
23	Summary of ICP Analyses of Shelburne Marble for Cations ^a	27
24	Average Annual Aerometric Data.....	28
25	Linear Regression Line Equations.....	28
26	Average Recession due to Sulfate Dissolution, per Rain Event (µm).....	28

**CHEMICAL ALTERATION OF LIMESTONE AND MARBLE SAMPLES
EXPOSED TO ACID RAIN AND WEATHERING IN THE
EASTERN UNITED STATES, 1984-1988**

by

K. J. Reimann

ABSTRACT

In a long-term program that began in 1984, limestone and marble briquettes have been exposed to both anthropogenic acid deposition and natural weathering at four field sites in the eastern United States. Similar tests began at an Ohio site in 1986. Effects of exposure on the briquettes and other materials at the sites are evaluated periodically by several federal agencies cooperating in the National Acid Precipitation Assessment Program (NAPAP). A primary contribution of Argonne National Laboratory to the NAPAP has been chemical analysis to determine changes in the samples caused by exposure to the environment. Wet chemical analysis was used to detect sulfates, nitrates, fluorides, chlorides, and a series of metal cations in sequential layers of stone removed from the briquettes after field exposure. Results from the first four years of the program indicate that rinsing by rain keeps skyward-facing stone relatively clean of reaction products, especially sulfate, the most abundant product. On groundward-facing samples, sulfate concentrations increased linearly with exposure time, and values were proportional to atmospheric SO₂ concentrations at the site. Sulfate concentrations in groundward samples were much higher in limestone than in marble, because of the greater porosity of the limestone. A steep sulfate gradient was seen in both sample types from the surface to the interior. On skyward surfaces, material losses per rain event due to complete dissolution of accumulated sulfates were approximately equal to concentrations measured in runoff. Preexposed limestone samples had sulfate accumulations deep in their interiors, while fresh, unexposed limestone did not. No substantial changes in cation accumulations were detected in either limestone or marble.

1 INTRODUCTION

The effects of acid rain and weathering on marble and limestone samples exposed to the outdoor environments at test sites in the eastern United States are being investigated as part of the National Acid Precipitation Assessment Program (NAPAP).^{1,2} The research is concerned with the direct effects on the stone materials of ambient gaseous pollutants such as sulfur dioxide and nitrogen oxides, and of acidic radices in the atmospheres at the sites. In addition, concentrations of several metallic elements, such as vanadium and lead, on the sample surfaces were initially monitored. The investigations are aimed at assessing the individual and combined contributions of various factors to stone alteration.

Several federal agencies are participating in the NAPAP. Investigators apply a variety of methods to measure stone deterioration, including gravimetry, surface metrology, mineralogy, rain-runoff chemistry, and chemistry of stone surfaces. Quantitative wet chemistry of thin layers of stone removed from sample surfaces is one of several tasks performed by Argonne

National Laboratory (ANL), which participates in the NAPAP studies as a facility of the U.S. Department of Energy. The ANL effort is sponsored by the U.S. National Park Service (NPS), which coordinates all the stone-materials research in cooperation with the U.S. Geological Survey (USGS).

A site management plan for field exposure of the stones³ was issued by the NPS in 1984. This plan detailed a projected 10-yr schedule of experiments, described stone procurement and sample fabrication, and contained protocols for handling and exposure of samples. Installation of stone slabs for analysis of rain runoff by USGS and of briquettes for other investigations, including ANL's wet chemistry, began in May 1984 at four established NAPAP test sites, which are near Raleigh, NC; Chester, NJ; Newcomb, NY; and in Washington, DC. An additional site was developed in Steubenville, OH, in 1986. The sites (designated NC, NJ, NY, DC, and OH, respectively) are instrumented to record a wide range of environmental parameters.

At the Ohio site, beginning in 1987, briquettes were installed in a movable rack that slides into a shelter when a rain event begins. Inside the shelter, some of the briquettes are sprayed with deionized water in the same quantity per surface area as the rain (sprayed regime), while the remaining briquettes stay dry (dry regime). At the end of the rain event, the movable rack leaves the shelter to be exposed to the normal environment.

To study the effects of long-term exposure, slabs of limestone and marble were obtained from buildings destined for demolition or renovation. From these preexposed slabs, briquettes were fabricated and installed at the test sites. The limestone slabs had been preexposed for 80 yr; and the marble slabs, 20 yr. Two types of briquettes were fabricated: one had the pre-exposed surface facing skyward, while the other had the preexposed surface facing groundward.

This topical report details the wet-chemistry procedures and the data obtained from analyses of stone briquettes exposed at the test sites from 1984 to 1988. Results that were previously published or otherwise reported^{4,5} are included. Additional data from samples subsequently withdrawn from field exposure will be provided in future reports.

Sample preparation procedures are summarized in Section 2 and detailed in Appendix A of this report. Appendix B includes (1) the section of the site management plan that specifies how briquettes exposed at the field sites are to be handled for wet-chemistry analysis, (2) the long-range plan for exposure of samples for analysis by wet chemistry, and (3) specifications for sample handling by site operators.

The protocol for wet-chemistry analysis of the stone briquettes was developed as part of the ANL effort in the NAPAP/NPS program. The protocol, summarized in Section 2 and detailed in Appendix C, was approved by the NPS Stone Research Group in 1984 and again in an updated form in 1985; it was approved by NAPAP peer reviewers in April 1986.

The analyses, performed on field-exposed samples according to quarterly, annual, and multiyear schedules (in accordance with the site management plan) used ion chromatography (IC) and inductively coupled plasma spectrometry (ICP). The results are summarized in Section 3 and detailed in Appendix D of this report; they are discussed and interpreted in Section 4.

2 SUMMARY OF EXPERIMENTAL PROCEDURES

Preparation of Briquettes for Exposure

Salem Limestone from Indiana and Shelburne Marble from Vermont were obtained as specimen stock materials by USGS and the National Bureau of Standards (NBS) for the NPS Stone Research Group.^{6,7} Slabs of previously unexposed material were cut by the suppliers from two monolithic blocks, with the geological bedding planes of the stone parallel to the broad faces of the slabs. Selected slabs were sectioned into specimen briquettes. The upper surface of limestone specimens was "smooth planed," whereas the marble had an 80-grit ground surface. These commercial finishes were produced by the suppliers and were not altered before field exposure. The bottom and cut surfaces of briquettes sectioned from the slabs by the NBS were unmodified after cutting; when additional briquettes were fabricated after a transfer of the archive and resupply stocks of stone to ANL in August 1984, surfaces other than the upper surface were finished by 180-grit wet-grinding of limestone and 80-grit wet-grinding of marble. Tap water was used as a coolant for all cutting and finishing.

The Stone Research Group recommended that chemical precleaning, not typically done when dimension stone is used in buildings and monuments, be avoided when preparing samples for exposure. It was recognized that impurities acquired during the formation of the materials and from the coolant could be quantitatively identified, and that the precleaning decision could be reversed, if necessary, during the study. However, the Group recommended care in handling the fabricated specimens to prevent contamination by oils and other extraneous substances, as well as protection of specimens in sealed polyethylene wrap until use. Due care was reportedly exercised and protective wraps were applied by NBS personnel, who prepared the initial briquettes. The precautions were maintained when additional briquettes were fabricated by ANL.

The dimensions of briquettes used in surface chemistry and other studies are shown in Fig. 1. The briquettes were water-rinsed, allowed to air-dry, labeled to preserve information regarding their locations and orientations in the source blocks, and stored in sealed Ziploc bags for further disposition.

Fig. 1.
Dimensions and Layer
Designation of Briquette
Specimens

Procedure for Briquette Exposure at Field Sites

Locations of the field exposure sites are noted in Section 1 of this report and detailed in Ref. 3. The access-controlled sites were instrumented to record environmental data and were monitored by site operators.

Acrylic exposure racks, produced by NBS, supported the briquettes at a 30° angle from the horizontal, inclined toward the south.³ The racks and wedge-shaped sample design securely protected the samples from displacement (e.g., by wind) while avoiding binding forces on specimens and providing minimum contact between specimen and rack.

Three briquettes each of limestone and marble were exposed in each test cycle at each site. The test cycles consisted of quarterly, annual, and multiyear periods of exposure. After each test cycle, the retrieved briquettes were replaced by new ones, as specified in the site management plan.³ Dates of sample installation, exchange, and removal are listed in Table 1. Handling, installation, monitoring, and removal of briquettes at the field sites followed specific protocols, which are described in Appendix B.

After removal from field racks under dry conditions, the exposed briquettes designated for wet-chemistry analysis were protected in sealed Ziploc bags, wrapped individually in layers of plastic bubble wrap, packed in padded, hard-cased containers, and shipped by ground transportation to ANL for analysis.

Postexposure Shaving of Briquette Surfaces

Specific areas of the briquette surfaces (Fig. 1) were shaved (i.e., precisely machined) to provide powders for analysis. Shaving practices are detailed in Appendix A. Approximately one-third of the area of each briquette top and/or bottom surface was sampled: material was removed from sequential layers at successive depths from the standardized locations on the briquette surfaces; each layer was 0.25 mm thick x 27 mm x briquette width (nominally 75 mm). The layers were assigned letters, as shown in Fig. 1. The powder from each layer, weighing approximately 1 g, was recovered separately, placed in a labeled, glass sample bottle, and capped.

Analyses were performed on powder samples from various layers that were selected according to specifications of the NPS Stone Research Group.

Preanalysis Apportioning and Aggregation of Powders

Each powder sample obtained from the briquettes was divided to provide a 450-550-mg aliquot for anion analysis; the remainder was allotted for cation analysis. If the remainder was greater than 550 mg, a 450-550 mg aliquot was used for cation analysis and the remainder was archived. The weight of each aliquot was determined to within 1 mg.

Table 1. Installation and Removal Dates of Previously Unexposed Limestone and Marble Briquettes at Various Field Exposure Sites for Stone Surface Wet Chemistry and Mineralogical Profiling

Sample, Procedure	NC	NJ	NY	DC	OH
Quarterly					
Install	5-25-84	6-05-84	6-19-84	8-11-84	8-17-86
Remove	8-24-84	9-07-84	9-25-84	11-15-84	10-20-86
Install	8-24-84	9-07-84	9-25-84	11-15-84	10-20-86
Remove	11-26-84	12-14-84	12-21-84	2-14-85	2-02-87
Install	11-26-84	12-14-84	12-21-84	2-14-85	2-02-87
Remove	3-01-85	3-06-85	3-20-85	5-13-85	4-21-87
Install	3-01-85	3-06-85	3-20-85	5-13-85	4-21-87
Remove	5-16-85	6-07-85	6-21-85	8-12-85	7-28-87
Install	5-16-85	6-07-85	6-21-85	8-12-85	-
Remove	8-28-85	9-20-85	9-23-85	11-12-85	-
Install	8-28-85	9-20-85	7-08-88	8-19-87	-
Remove	11-17-85	12-06-85	11-01-88	11-19-87	-
Install	11-17-85	-	11-01-88	11-14-87	-
Remove	3-03-86	-	2-20-89	2-17-88	-
Install	3-03-86	-	-	2-17-88	-
Remove	6-04-86	-	-	6-08-88	-
Install	-	-	-	6-08-88	-
Remove	-	-	-	9-14-88	-
Annual					
Install	5-25-84	6-05-84	6-19-84	8-11-84	7-17-86
Remove	5-16-85	6-07-85	6-21-85	8-12-85	7-28-87
Install	5-16-85	6-07-85	6-21-85	8-12-85	7-28-87 ^a
Remove	6-04-86	6-18-86	6-26-86	8-14-86	8-10-88
Install	6-09-87	-	6-25-87	8-11-87	-
Remove	7-06-88	-	7-08-88	9-14-88	-
Biennial					
Install	5-25-84	6-05-84	6-19-84	8-11-84	7-17-86
Remove	6-04-86	6-16-86	6-26-86	8-14-86	8-10-88
Triennial					
Install	5-25-84	-	6-19-84	8-11-89	-
Remove	6-09-87	-	6-25-87	8-11-87	-
Quadrennial					
Install	5-25-84	-	6-19-84	8-11-84	-
Remove	7-06-88	-	7-08-88	9-14-88	-

^aStationary and movable rack.

For economy of analysis, some samples were prepared by powder aggregation. Powders obtained from layers at the same depth from the same surface (top or bottom) of replicate briquettes were aggregated when specified by the NPS Stone Research Group. Portions of equal weight (within 10%) were taken from the specified powders and mixed together to form the aliquots for anion and cation analyses.

The final weights of the powder aliquots were reduced to 225-275 mg and determined to within 1 mg. The amount of powder used was reduced because we were concerned that, for samples undergoing prolonged exposure and containing large concentrations of surface sulfate, the effects of solubility limits might interfere during a leaching process used to bring anions into solution for analysis.

Analytical Procedures

Anions of primary interest to the NPS Stone Research Group were the sulfate, nitrate, chlorine, and fluorine contained in reaction products and deposited on the calcium carbonate stone materials. These ions were quantitatively determined by leaching weighed samples of the powdered stone in an aqueous solution and then analyzing the solution by IC. The leaching

solution consisted of 0.003 M NaHCO_3 -0.0025 M Na_2CO_3 in water; 20 mL of this solution was equilibrated with each powder quantity specified for IC analysis. A portion of the leachate was then filtered and injected into Dionex ion chromatograph. The procedures are detailed in Appendix C.

Cations were determined by ICP after dissolution of stone powders in a hydrochloric acid solution, as detailed in Appendix C. Results included metals originally in the stone as well as those in surface products; the contributions of the latter, if any, to the concentrations of the cations, must be derived by comparing results from exposed and unexposed samples. Metals of particular interest were cadmium, zinc, lead, vanadium, manganese, aluminum, strontium, and magnesium.

3 RESULTS

Averages and standard deviation of the results of surface chemistry analyses were calculated according to stone type, layer, and exposure site and period; they are summarized in Tables 2-21 for IC and Tables 22 and 23 for ICP. Analytical results of control briquettes (baseline) of fresh and preexposed briquettes and of bulk powders are included for comparison.

The standard deviation was calculated as follows:

$$\sigma = \left[\frac{\sum (x - \bar{x})^2}{N} \right]$$

Table 2. Summary of IC Analyses of Control Samples for Anions ($\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Limestone			Marble		
Sulfate						
A	160	± 10	88	<15	<15	Bulk
B	82.5	± 7.5	72	<15	<15	
C	77.5	± 7.5	65	<15	<15	
X	68					
Y	68					
Z	80					
Nitrate						
A	<15		<15	<15	<15	Bulk
B	<15		<15	<15	<15	
C	<15		<15	<15	<15	
X	<15			<15	<15	
Y	<15			<15	<15	
Z	<15			<15	<15	
Fluorine						
A	<10		4	<5	<5	Bulk
B	<10		5	<5	<5	
C	<10		5	<5	<5	
X	5			<5	<5	
Y	5			<5	<5	
Z	4			<5	<5	
Chlorine						
A	42.5	± 12.5	35	<5	9	Bulk
B	33.0	± 5.0	26	<5	5	
C	32.5	± 2.5	24	4	4	
X	23			4		
Y	24			4		
Z	28			4		

Table 3. Summary of IC Analyses of Limestone from the North Carolina Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-F, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion. Layer	Quarterly								Annual		Biennial	
	1984-85				1985-86				First	Second	1984-86	
	1	2	3	4	5	6	7	8				
Sulfate												
A	80.0 $\pm$ 10.8	119.7 $\pm$ 10.3	93.0 $\pm$ 2.2	64.3 $\pm$ 5.3	65	65	130	90	54.7 $\pm$ 0.9	90 ^a	100.0 $\pm$ 4.1	
B	76.7 $\pm$ 10.3	89.7 $\pm$ 7.9	86.7 $\pm$ 1.7	66.0 $\pm$ 4.1	65	70	100	70	62.75 $\pm$ 3.4	60 ^a	85 $\pm$ 14.7	
C	77.0 $\pm$ 8.2	89.0 $\pm$ 6.7	82.3 $\pm$ 1.3	65.3 $\pm$ 4.2	-	-	-	-	67.0 $\pm$ 10.6	70 ^a	80 $\pm$ 4.1	
X	135	132	200	118	-	-	-	-	225	360	330	
Y	178	247	208	115	185	120	295	680	260	405	505	
Z	2105 $\pm$ 15	2908	2550	121	1245	520	270	3635	6197 $\pm$ 736	9550	11238 $\pm$ 1563	
Nitrate												
A	<15	<15	<10	25.5 $\pm$ 0.5	15	<15	<15	20	8 $\pm$ 0.0	20 ^a	20 $\pm$ 0.0	
B	<15	<15	<10	26.3 $\pm$ 16.9	15	<15	<15	<15	10 $\pm$ 2.0	15 ^a	<15	
C	<15	<15	<10	14.7 $\pm$ 2.5	-	-	-	-	12 $\pm$ 1.0	<15 ^a	<15	
X	15	56	16	<10	-	-	-	-	21	240	200	
Y	14	53	13	10	35	<15	335	110	22	240	205	
Z	39.5 $\pm$ 10.5	73	14	10	<15	20	15	105	67.5 $\pm$ 36.5	290	176 $\pm$ 148	
Fluorine												
A	<10	6 $\pm$ 1.0	4 $\pm$ 0.0	5.0 $\pm$ 0.7	5	5	10	7	5.7 $\pm$ 1.7	5 ^a	5.0 $\pm$ 0.0	
B	<10	<5	4 $\pm$ 0.0	5.0 $\pm$ 0.7	5	5	10	5	7.0 $\pm$ 1.6	5 ^a	5.0 $\pm$ 0.0	
C	<10	<5	4 $\pm$ 0.5	4.3 $\pm$ 0.5	-	-	-	-	6.7 $\pm$ 0.9	5 ^a	5.0 $\pm$ 0.0	
X	6	10	6	5	-	-	-	-	11	10	10	
Y	6	9	6	5	10	10	10	10	11	10	10	
Z	7	11	6	5	10	10	10	10	8.5 $\pm$ 0.5	15	16.5 $\pm$ 3.5	
Chlorine												
A	18.3 $\pm$ 2.4	17.7 $\pm$ 1.9	16.7 $\pm$ 0.9	32.0 $\pm$ 8.5	20	15	15	20	18.0 $\pm$ 1.6	25 ^a	20.0 $\pm$ 0.0	
B	21.7 $\pm$ 2.4	20.3 $\pm$ 3.1	18.7 $\pm$ 0.5	28.7 $\pm$ 0.9	20	20	20	20	19.7 $\pm$ 1.9	25 ^a	21.3 $\pm$ 2.4	
C	23.3 $\pm$ 4.7	21.7 $\pm$ 4.0	19.3 $\pm$ 1.3	27.7 $\pm$ 0.5	-	-	-	-	19.7 $\pm$ 2.1	25 ^a	21.7 $\pm$ 2.4	
X	34	64	28	27	-	-	-	-	24	60	45	
Y	34	60	27	26	25	20	30	60	25	60	45	
Z	39.5 $\pm$ 5.5	68	26	23	25	20	25	105	31 $\pm$ 9	65	56 $\pm$ 1	

^aDenotes analysis of aggregated powders.

Table 4. Summary of IC Analyses of Limestone from the North Carolina Site for Anions, Annual, and Multiyear Exposures (Layers A and U-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion. Layer	Third Annual 1987-88		Triennial 1984-87		Quadrennial 1984-88	
Sulfate						
A	59.5 $\pm$ 0.5		112 $\pm$ 3.3		55.3 $\pm$ 0.5	
U	110		-		181.0 $\pm$ 71.0	
V	112		-		169.5 $\pm$ 46.5	
W	127		-		215 $\pm$ 88	
X	169 $\pm$ 34		598 $\pm$ 131		258.3 $\pm$ 91.3	
Y	457 $\pm$ 143		1913 $\pm$ 1276		1123 $\pm$ 203	
Z	10750 $\pm$ 1750		22000 $\pm$ 2121		19433 $\pm$ 1053	
Nitrate						
A	<17		10.3 $\pm$ 1.9		35 $\pm$ 1	
U	162		-		87 $\pm$ 5	
V	148		-		86 $\pm$ 11	
W	144		-		81 $\pm$ 9	
X	141 $\pm$ 3		90.7 $\pm$ 8.7		65.3 $\pm$ 3.7	
Y	117.5 $\pm$ 7.5		91.7 $\pm$ 11.4		63.7 $\pm$ 4.0	
Z	162.5 $\pm$ 32.5		146.7 $\pm$ 16.5		107 $\pm$ 5.0	
Fluorine						
A	15 $\pm$ 0.0		6 $\pm$ 0.0		13.3 $\pm$ 3.8	
U	17		-		19.5 $\pm$ 0.5	
V	17		-		19.5 $\pm$ 0.5	
W	18		-		20.0 $\pm$ 0.0	
X	18.5 $\pm$ 0.5		15.3 $\pm$ 3.8		18.0 $\pm$ 4.2	
Y	19 $\pm$ 0		19.0 $\pm$ 6.5		20.7 $\pm$ 4.8	
Z	20.5 $\pm$ 0.5		34.7 $\pm$ 2.5		38.8 $\pm$ 7.6	
Chlorine						
A	15 $\pm$ 1		16.7 $\pm$ 1.7		20.0 $\pm$ 0.8	
U	43		-		29.0 $\pm$ 1.0	
V	40		-		26.5 $\pm$ 1.5	
W	40		-		28.0 $\pm$ 0.0	
X	38.0 $\pm$ 0.0		46.7 $\pm$ 4.0		24.3 $\pm$ 2.9	
Y	39 $\pm$ 2		53.7 $\pm$ 8.7		26.7 $\pm$ 4.1	
Z	40.5 $\pm$ 0.5		50.3 $\pm$ 9.0		23.3 $\pm$ 2.4	

where $\bar{x}$ is the ppm of briquette, $\bar{x}$ is the average ppm of briquette, and N is the number of briquettes (generally $N = 3$).

N was chosen as the weighting factor for standard deviation because it results in a maximum-likelihood estimation generally used to describe populations. The term $(N-1)$ is an unbiased estimator customarily used for sampled data.

In calculating the averages, extreme values were omitted. Monitoring at the NJ site was discontinued in 1986; therefore, results from this site are limited to those for 1984–1986. The changes in cation concentration obtained by ICP analysis were insignificant. Therefore, this test was suspended after 1986, following consultation with the NPS.

Detailed data for each analyzed layer of each briquette by site and exposure period, as recorded on disc with Lotus 1-2-3 or ASCI, are found in Appendix D. Data recorded on the disc are regularly updated to include the latest results.

4 DISCUSSION AND CONCLUSIONS

The average anion concentrations, tabulated in the previous section, indicate a difference between limestone and marble. Concentrations of sulfate, nitrate, fluoride and chlorine are higher in the control samples (prior to exposure) and bulk limestone than in marble. The sulfate concentration generally plays the most active role. A typical distribution of sulfate among the various layers of specimens from the NC site is shown in Fig. 2. The largest sulfate concentrations are observed in the groundmost layer (Z in Fig. 1), which is protected from rinsing by incident rainfall. Similar, but significant, levels of sulfate were observed in layers X and Y, which are further inward. A sharp sulfate concentration gradient, which reached bulk concentration values past layer U, was observed.

In contrast, very little change in sulfate concentration was observed in the most skyward, rain-washed layer (A in Fig. 1). No sulfate accumulation was detected in layers B and C above the baseline levels observed for unexposed stones. The time dependence of sulfate concentration on the test briquettes from the five NAPAP sites can be seen in Figs. 3 and 4. Figure 3 shows the sulfate levels in the A layer after quarterly, annual, biennial, triennial, and quadrennial exposure times. Very little, if any, sulfate accumulated on either the marble or limestone briquettes at the NC, NJ, and NY sites. The DC briquettes showed a gradual increase in sulfate concentration during the first three years of exposure, while those from OH exhibited a much higher sulfate levels than briquettes from the other four sites.

Fig. 2. Sulfate Distribution among Layers for the NC Site. Legend: + Quarterly; Δ Annual; □ Biennial; ▲ Triennial; ■ Quadrennial

Fig. 3. Average Sulfate Concentration in the Topmost, Skyward, A, Layer of the (a) Marble and (b) Limestone Test Briquettes from the Five NAPAP Materials Exposure Sites after 0.25, 1, 2, 3, and 4 Yr of Exposure

Fig. 4. Average Sulfate Concentration in the Outermost, Groundward Z, Layer of the (a) Marble and (b) Limestone Test Briquettes from the Five NAPAP Materials Exposure Sites after 0.25, 1, 2, 3, and 4 Yr of Exposure

Table 5. Summary of IC Analyses of Limestone from the New Jersey Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, µg/g; Average ± standard deviation given for analyses of replicate samples)

Anion. Layer	1984 - 1985 Quarterly				Annual		Biennial
	1	2	3	4	First	Second	1984-86
Sulfate							
A	96.7 ± 4.7	225.3 ± 25.9	120.3 ± 8.3	76.3 ± 1.3	78.3 ± 5.7	75 ^a	63.3 ± 4.7
B	85.0 ± 4.1	22.7 ± 1.9	103.3 ± 3.9	79.7 ± 3.7	79.7 ± 1.7	75 ^a	70.0 ± 0.0
C	71.1 ± 10.3	104.7 ± 5.3	96.7 ± 1.7	75.6 ± 3.4	77.7 ± 1.3	70 ^a	70.0 ± 7.1
X	188	14.7	191	264	440	570	470
Y	189	170	252	252	1150	500	490
Z	4904	3176	4310	5190	11142	12900	14490 ± 4510
Nitrate							
A	<15	<15	<10	<10	<9	<15 ^a	<15
B	<15	<15	<10	<38	<9	<15 ^a	<15
C	<15	<15	<10	<10	<9	<15 ^a	<15
X	41	22	20	36	34	15	20
Y	33	27	17	36	39	15	20
Z	71	38	25	47	90.5 ± 1.5	25	50.5 ± 10.5
Fluorine							
A	<10	<7	4.0 ± 0.0	3.7 ± 0.5	4.0 ± 0.0	10 ^a	5.0 ± 0.0
B	<10	<7	4.3 ± 0.5	4.0 ± 0.0	4.0 ± 0.0	10 ^a	8.3 ± 2.4
C	<10	<7	4.7 ± 0.5	4.0 ± 0.0	4.0 ± 0.0	10 ^a	8.3 ± 2.4
X	6	11	6	6	6	10	10
Y	6	10	6	6	7	10	10
Z	6	12	6	6	7.5 ± 1.5	10	13.0 ± 2.0
Chlorine							
A	23.3 ± 4.7	18.0 ± 1.4	19.7 ± 2.1	19.7 ± 0.9	20.0 ± 0.8	25 ^a	15.0 ± 0.0
B	25.0 ± 4.1	19.3 ± 2.6	21.3 ± 1.7	22.7 ± 0.9	21.7 ± 0.9	25 ^a	16.7 ± 2.4
C	18.3 ± 2.4	18.7 ± 2.4	21.3 ± 0.9	22.0 ± 0.8	22.0 ± 1.6	20 ^a	18.3 ± 2.4
X	31	30	34	33	27	25	25
Y	36	29	32	32	27	25	20
Z	34	30	36	33	32.0 ± 2.0	25	23.0 ± 3.0

^aDenotes analysis of aggregated powders.

Table 6. Summary of IC Analyses of Limestone from the New York Site for Anions, Quarterly, Annual, and Multiyear Exposures (Layers A-C and X-Z, µg/g; Average ± standard deviation given for analyses of replicate samples)

Anion. Layer	1984 - 1985 Quarterly				Annual		2 yrs
	1	2	3	4	First	Second	1984-86
Sulfite							
A	60.0 ± 10.8	65.3 ± 1.9	72.7 ± 4.1	57.7 ± 6.3	66.3 ± 16.1	80 ^a	51.7 ± 2.4
B	63.3 ± 10.3	66.0 ± 3.6	71.3 ± 2.5	61.7 ± 3.7	62.7 ± 2.1	75 ^a	61.7 ± 2.4
C	63.3 ± 12.5	62.7 ± 1.3	68.7 ± 3.4	63.0 ± 4.1	63.7 ± 2.5	70 ^a	61.7 ± 2.4
X	126	76	186	122	100	95	110
Y	134	85	191	124	110	100	115
Z	1499	91	1040	126	1100	120	1214 ± 84
Nitrate							
A	<15	<15	<10	17.3 ± 4.6	<9	<15 ^a	<15
B	<15	<15	<10	14.0 ± 5.0	<9	<15 ^a	<15
C	<15	<15	<10	12.7 ± 0.5	<9	<15 ^a	<15
X	<12	<15	<10	10	11	<15	15
Y	<12	<15	10	10	15	<15	<15
Z	<12	<15	10	12	20	<15	<15
Fluorine							
A	<10	<5	3.7 ± 0.5	5.0 ± 0.8	6.0 ± 0.8	10 ^a	<5
B	<10	<5	4.0 ± 0.0	4.7 ± 0.5	6.0 ± 0.0	10 ^a	<5
C	<10	<5	4.3 ± 0.5	4.3 ± 0.5	5.7 ± 0.5	5 ^a	5.0 ± 0.0
X	6	9	5	5	5	10	5
Y	6	9	6	5	4	10	5
Z	6	9	5	5	7	10	9.0 ± 1.0
Chlorine							
A	18.3 ± 2.4	20.3 ± 1.9	16.0 ± 0.8	27.3 ± 4.5	18.0 ± 1.6	20 ^a	16.7 ± 2.4
B	20.0 ± 0.0	22.3 ± 2.1	18.0 ± 0.8	24.7 ± 0.5	18.7 ± 0.5	20 ^a	20.0 ± 0.0
C	20.0 ± 0.0	22.3 ± 1.3	18.0 ± 0.8	23.3 ± 0.5	19.7 ± 2.4	20 ^a	21.7 ± 2.4
X	28	24	26	28	21	20	20
Y	27	25	20	23	20	20	20
Z	26	24	22	24	21	20	21.0 ± 1.0

^aDenotes analysis of aggregated powders.

Table 7. Summary of IC Analyses of Limestone from the New York Site for Anions, Annual and Multiyear Exposures (Layers A and U-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Third Annual 1987-88		Triennial 1984-87		Quadrennial 1984-88	
Sulfate						
A	49.7 ±	4.8	55.7 ±	2.5	41.3 ±	1.9
U	92.0 ±	0.0	-	-	.84 ±	10
V	-	-	-	-	-	-
W	104	-	-	-	-	-
X	120.5 ±	6.5	220 ±	85	75	-
Y	181 ±	13	222 ±	37	-	-
Z	2683 ±	379	4595 ±	1929	7005	-
Nitrate						
A	<17	-	7.0 ±	0.0	<17	-
U	28 ±	9	-	-	<17	-
V	-	-	-	-	-	-
W	23	-	-	-	-	-
X	21 ±	3	23.0 ±	4.2	<17	-
Y	29.5 ±	5.5	23.3 ±	4.7	-	-
Z	36.3 ±	7.0	34.3 ±	11.4	23	-
Fluorine						
A	<8	-	4.3 ±	0.5	8.0 ±	0.0
U	9.5 ±	0.5	-	-	10.0 ±	0.0
V	-	-	-	-	-	-
W	8	-	-	-	-	-
X	9.0 ±	0.0	19.3 ±	0.5	<7	-
Y	10 ±	0.0	17.7 ±	2.1	-	-
Z	10.3 ±	0.5	20.7 ±	1.3	22 ±	-
Chlorine						
A	15.3 ±	0.9	12.7 ±	0.9	17.7 ±	2.0
U	26.0 ±	2.0	-	-	15.5 ±	1.5
V	-	-	-	-	-	-
W	21	-	-	-	-	-
X	23 ±	4	43.6 ±	6.9	26	-
Y	23.5 ±	3.5	36.7 ±	6.2	-	-
Z	25.3 ±	2.1	30.7 ±	3.1	20	-

The higher sulfate concentrations in Layer A of the DC and OH briquettes can be explained by consulting Table 24. The lower rainfall (combined with fewer rain events) and higher H^+ concentration result in incomplete removal of the sulfate during the rain events, as well as formation of additional sulfates between the last rainfall and briquette removal. The error bars in Figs. 3 and 4 represent 1 standard deviation. Data for all quarterly and annual samples have been averaged, even though not all of the briquettes were exposed simultaneously for the same duration. Considerable scatter of the data can be explained by differences in temperature during various exposure periods (especially for quarterly briquettes), differences in day and night temperature, wind strength, and humidity, all of which affect the sulfate formation rate. The vertical scale of Fig. 2 also shows that sulfate concentration in limestone is more than twice as high as that in marble, probably because of the higher porosity, and thus larger reaction area of the limestone.

Sulfate buildup in the outermost groundward Layer Z is shown in Fig. 4. Because this layer is not rinsed by rain, the increase in sulfate concentration is proportional to the exposure time, humidity, temperature, and H^+ concentration, which varies by exposure site. The DC and OH sites exhibit the largest increase in sulfate concentration, in concurrence with Table 24 H^+ concentration. Within the scatter of the data, the accumulation of sulfate in the groundward layer appears to be linear. The linear regression lines can be expressed by the equations in Table 25.

Table 8. Summary of IC Analyses of Limestone from the Washington, DC, Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Quarterly																Annual		Biennial	
	1984-85				1987-88				1987-88				1987-88				First	Second	1984-86	
	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16				
Sulfate	245 83.3 68.3 220 602 5204	116 94.3 92.0 224 272 5408	101.0 49.0 95.7 152 173 1410	9.9 48 5.3 995 1202 4860	155.7 75.0 68.0 995 1202 4860	9.9 48 5.3 995 1202 4860	101.0 49.0 95.7 152 173 1410	9.9 48 5.3 995 1202 4860	155.7 75.0 68.0 995 1202 4860	9.9 48 5.3 995 1202 4860	101.0 49.0 95.7 152 173 1410	9.9 48 5.3 995 1202 4860	155.7 75.0 68.0 995 1202 4860	9.9 48 5.3 995 1202 4860	101.0 49.0 95.7 152 173 1410	9.9 48 5.3 995 1202 4860	155.7 75.0 68.0 995 1202 4860	9.9 48 5.3 995 1202 4860	101.0 49.0 95.7 152 173 1410	9.9 48 5.3 995 1202 4860
Nitrate	<15 15 15 15 15 15	<15 15 15 15 15 15	16.3 15.3 15.3 12 18 18	2.6 5.0 5.0 200 226 235	19.3 21.0 16.3 200 226 235	2.6 5.0 5.0 200 226 235	16.3 15.3 15.3 12 18 18	2.6 5.0 5.0 200 226 235	19.3 21.0 16.3 200 226 235	2.6 5.0 5.0 200 226 235	16.3 15.3 15.3 12 18 18	2.6 5.0 5.0 200 226 235	19.3 21.0 16.3 200 226 235	2.6 5.0 5.0 200 226 235	16.3 15.3 15.3 12 18 18	2.6 5.0 5.0 200 226 235	19.3 21.0 16.3 200 226 235	2.6 5.0 5.0 200 226 235	16.3 15.3 15.3 12 18 18	2.6 5.0 5.0 200 226 235
Fluorine	<5 5 5 5 5 5	<5 5 5 5 5 5	4.0 4.3 4.7 8 6 6	0.0 0.5 0.5 10 11 11	4.0 4.0 4.0 10 11 11	0.0 0.5 0.5 10 11 11	4.0 4.3 4.7 8 6 6	0.0 0.5 0.5 10 11 11	4.0 4.0 4.0 10 11 11	0.0 0.5 0.5 10 11 11	4.0 4.3 4.7 8 6 6	0.0 0.5 0.5 10 11 11	4.0 4.0 4.0 10 11 11	0.0 0.5 0.5 10 11 11	4.0 4.3 4.7 8 6 6	0.0 0.5 0.5 10 11 11	4.0 4.0 4.0 10 11 11	0.0 0.5 0.5 10 11 11	4.0 4.3 4.7 8 6 6	0.0 0.5 0.5 10 11 11
Chlorine	15.0 16.7 20.0 56.5 56.5 65.5	0.0 2.4 4.1 3.5 3.5 0.5	17.3 20.3 20.3 31 31 33	2.4 2.6 2.1 3.5 3.5 0.5	20.3 23.0 23.0 115 121 127	2.4 2.6 2.1 3.5 3.5 0.5	17.3 20.3 20.3 31 31 33	2.4 2.6 2.1 3.5 3.5 0.5	20.3 23.0 23.0 115 121 127	2.4 2.6 2.1 3.5 3.5 0.5	17.3 20.3 20.3 31 31 33	2.4 2.6 2.1 3.5 3.5 0.5	20.3 23.0 23.0 115 121 127	2.4 2.6 2.1 3.5 3.5 0.5	17.3 20.3 20.3 31 31 33	2.4 2.6 2.1 3.5 3.5 0.5	20.3 23.0 23.0 115 121 127	2.4 2.6 2.1 3.5 3.5 0.5	17.3 20.3 20.3 31 31 33	2.4 2.6 2.1 3.5 3.5 0.5

^aDenotes analysis of aggregated powders.

Table 9. Summary of IC Analyses of Limestone from the Washington, DC, Site for Anions, Annual and Multiyear Exposures (Layers A and U-Z $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Third Annual 1987-88		Triennial 1984-87		Quadrennial 1984-88	
Sulfate						
A	198	± 19	303	± 15	195	± 20
U	263	± 65	-	-	165	± 25
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	439	-	793	± 38	596	-
Y	-	-	2528	± 133	-	-
Z	18433	± 1636	34000	± 6377	38467	± 8930
Nitrate						
A	37.3	± 3.8	65	± 4	36.3	± 6.7
U	668	± 3	-	-	171	± 23
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	615	-	470	± 115	424	-
Y	-	-	470	± 80	-	-
Z	792	± 21	700	± 150	589	± 52
Fluorine						
A	<7	-	6.7	± 0.9	<9	-
U	<7	-	-	-	<10	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	<7	-	9.8	± 0.2	10	-
Y	-	-	11.7	± 2.4	-	-
Z	8	± 1	50.0	± 8.2	27.3	± 2.1
Chlorine						
A	21.0	± 0.8	40.0	± 4.1	20.0	± 1.6
U	154	± 25	-	-	44	± 0
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	123	-	75	± 5	77	-
Y	-	-	88	± 18	-	-
Z	160	± 33	98	± 28	62	± 13

The considerable data scatter may reflect simultaneous loss and gain of sulfate due to removal by washing, seepage between briquettes and support rods, and/or secondary deposition processes. In both types of stone briquettes, a darker area appears on the surface of the Z layer in the region between the supporting rods shown in Fig. 5. The color of the area darkens with exposure time and shrinks in size due to dissolution of sulfate at two edges of the groundward surface. Because the powders for analysis are obtained by shaving a 1-in. (2.54-cm)-wide path through the center of the gypsum spot, they will contain higher (dark area) and lower (light area at the edges) concentrations of sulfate. If the sulfate concentration in the light area is assumed to be similar to that in the skyward surface, the measured sulfate concentration can be corrected to represent the actual concentration of the dark spot. The ratio of the total shaved area to the dark shaved area yields the desired correction factors, which are approximately

- quarterly exposure 1.00 or same as measured.
- annual exposure 1.17 or 17% increase.
- triennial exposure 1.28 or 28% increase.

Table 10. Summary of IC Analyses of Limestone from the Ohio Site for Anions, Quarterly, Annual, and Biennial Exposures ($\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Quarterly									Annual					Biennial	
	1986-87									1986-87 First		Anion Layer	1987-88 Second		1986-88	
	9	10	11	12	13	14	15	16	17	18	19		20			
Sulfate																
A	239	± 24	162	± 13	210	± 4	586	± 8.5	558	± 8.5	A	303	± 38.3	321	± 12.4	
B	-	-	-	-	-	-	-	-	175	-	U	-	-	-	-	
C	-	-	-	-	-	-	-	-	135	-	U	347.5	± 39.5	-	-	
X	350	± 8	378	± 55	420	± 0	342	± 62	493	± 129	X	361	-	618	± 119	
Y	625	± 90	472	± 44	440	-	537	± 158	1053	± 172	Y	-	-	-	-	
Z	7400	± 100	6742	± 806	7675	± 125	8247	± 1129	18333	± 1247	Z	22500	± 1100	29400	± 1178	
Nitrate																
A	11	± 1.6	13.7	± 1.7	13	± 1	20	± 0	16.7	± 2.4	A	<21	-	<27	-	
B	-	-	-	-	-	-	-	-	15	-	U	-	-	-	-	
C	-	-	-	-	-	-	-	-	15	-	U	242	± 7	-	-	
X	26.3	± 4.6	70	± 11	34	± 4	122	± 2	125.0	± 14.1	X	210	-	165	± 12.5	
Y	26.3	± 3.8	72	± 10	32.5	± 1.5	120	± 0	121.7	± 13.1	Y	-	-	-	-	
Z	27.7	± 1.9	82	± 15	40	± 2	133	± 6	145.0	± 14.7	Z	247	± 27	227	± 12	
Fluorine																
A	5.3	± 0.5	5.0	± 0.0	5	± 0	7.7	± 0.5	7.3	± 0.5	A	9.3	± 0.9	8	± 0	
B	-	-	-	-	-	-	-	-	5	-	U	-	-	-	-	
C	-	-	-	-	-	-	-	-	5	-	U	10.5	± 0.5	-	-	
X	15.3	± 4.0	17.3	± 2.5	19.5	± 4.5	7.9	± 0.4	9.0	± 0.4	X	11	-	10.7	± 0.5	
Y	17.3	± 2.5	18.0	± 2.8	15.5	± 1.5	8.3	± 0.3	9.7	± 0.5	Y	-	-	-	-	
Z	14.0	± 0.0	13.1	± 3.4	15.5	± 0.5	9.7	± 0.4	15.0	± 0.0	Z	13.3	± 1.2	24.3	± 2.4	
Chlorine																
A	18.3	± 0.5	18.3	± 2.1	19.0	± 1.0	28.3	± 2.4	30.0	± 0.0	A	18.7	± 2.9	18.3	± 3.7	
B	-	-	-	-	-	-	-	-	25	-	U	-	-	-	-	
C	-	-	-	-	-	-	-	-	30	-	U	100	± 3	-	-	
X	52	± 16	108.7	± 8.2	81.5	± 19.5	75.0	± 4.1	51.7	± 2.4	X	103	-	66.7	± 9.4	
Y	56.7	± 7.7	105.7	± 11.4	70.5	± 3.5	71.7	± 2.4	58.3	± 2.4	Y	-	-	-	-	
Z	46.0	± 4.3	91.0	± 5.0	64.5	± 0.5	76.7	± 6.2	53.3	± 2.4	Z	116	± 2.2	60.0	± 1.6

Fig. 5. Photographs of Groundward Surfaces of Limestone Test Briquettes After Exposed at the DC Site: after (a) 1 Quarter, (b) 1 Yr, and (c) 3 Yr

Table 11. Summary of IC Analyses
of Limestone from the Movable Rack
at the Ohio Site for Anions,
1987-88 ($\mu\text{g/g}$; Average $\pm$ standard
deviation given for analyses of
replicate sample)

Anion, Layer	Dry Regime		Sprayed Regime	
Sulfate				
A	257, 2580		419	± 36
U	555 ± 1		779	± 41
Z	1125 ± 3275		14350	± 1450
Nitrate				
A	34 ± 6		23	± 5
U	144.5 ± 0.5		173.5	± 29.5
Z	184.5 ± 8.5		206	± 37
Fluorine				
A	15 ± 1		11	± 1
U	8 ± 0		8.5	± 0.5
Z	25 ± 3		20.5	± 4.5
Chlorine				
A	25.5 ± 0.5		20	± 3
U	132 ± 2		166.5	± 21.5
Z	160 ± 2		190.5	± 11.5

The correction indicates that the rate at which sulfate accumulates is higher than measured, and that it increases with exposure time. It should be realized that in applying this correction, one assumes a uniform sulfate accumulation throughout the 0.25-mm-thick shaved layer. Other investigators, however, found that the gypsum layer is only about 100 μm thick. The averages in the tables and graphs are therefore not corrected. Comparison of H^+ concentrations in Table 24 with the slopes of the regression lines shows that the accumulation rates of sulfate in the Z layer can be qualitatively related to the average ambient concentration of H^+ at the five exposure sites: $\text{NY} < \text{NC} < \text{NJ} < \text{DC} < \text{OH}$. The difference in sulfate concentration between the A and Z layers demonstrates that most of the deposited sulfate is removed from the skyward surface during rain events.

Variations in nitrate, chlorine, and fluorine concentration follow a pattern similar to sulfate concentration. The concentration of these anions in the A layer shows very little, if any, change, due again to rinsing of the surface by rain events. The anion concentration in the Z layer increases with exposure time, but is several orders of magnitude smaller than the increase in sulfate concentration. Nitrate exhibits the highest rate of increase in the Z layer, followed by chlorine, and finally by fluorine. Limestone contains higher concentrations of these anions than marble. Accumulation rates of nitrate, chlorine, and fluorine in the Z layer can be qualitatively related to average ambient concentrations of H^+ at the site, and specimens from DC and OH show the greatest increases, while those from NY show the lowest.

A few annual briquettes were exposed in the movable rack in 1987 in OH. The sulfate accumulation in the A layer of the dry-regime briquettes was higher than in normally exposed briquettes, as anticipated, since the skyward surface was not rinsed. The briquettes in the sprayed regime exhibited a slightly lower sulfate accumulation in the A layer than did normally exposed briquettes, probably due to lower concentrations of SO_2 in the deionized rinsing water than in normal rain.

Table 12. Summary of IC Analyses of Marble from the North Carolina Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given fore analyses of replicate samples)

Anion, Layer	Quarterly								Annual				Biennial		
	1984-85				1985-86										
	1	2	3	4	5	6	7	8	First	Second	1984-86				
Sulfate															
A	<15	31.3 ± 5.3	<11.0	<13.5	<20 ^a	30 ^a	40 ^a	35 ^a	9.0 ± 0.8	35.0 ^a	<25				
B	<15	<15	11.0 ± 0.0	<10	-	-	-	-	<14	<20.0 ^a	<30				
C	<15	<15	<10	<10	-	-	-	-	<3	30.0 ^a	<20				
X	22	18	27	27	-	-	-	-	42	80	65				
Y	26	44	41	25	-	-	-	-	87	120	90				
Z	348 ± 108	665	458	534	375 ^a	255 ^a	445 ^a	345 ^a	2726 ± 249	1570	2773 ± 338				
Nitrate															
A	<15	<15	<10	<10	<15 ^a	<15 ^a	<30 ^a	<15 ^a	<8	<15 ^a	<15				
B	<15	<15	<10	<10	-	-	-	-	<8	<15 ^a	<15				
C	<15	<15	<10	<10	-	-	-	-	<8	<15 ^a	<15				
X	10	<8	16	10	-	-	-	-	17	15	<15				
Y	12	8	18	10	-	-	-	-	15	<15	<15				
Z	52.5 ± 11.5	33	47	59	35 ^a	25 ^a	25 ^a	70 ^a	64.5 ± 6.5	50	38 ± 7				
Fluorine															
A	<10	<5	<2	<5	<5 ^a	<5 ^a	<5 ^a	<5 ^a	<2	<5 ^a	<5				
B	<10	<5	<2	<2	-	-	-	-	<2	<5 ^a	<5				
C	<10	<5	<2	<2	-	-	-	-	<2	<5 ^a	<5				
X	<2	<3	<2	<2	-	-	-	-	4	<5	<5				
Y	2	<3	<2	<2	-	-	-	-	4	<5	<5				
Z	3.5 ± 1.5	3	2	3	5 ^a	5 ^a	5 ^a	5 ^a	14.5 ± 4.5	10	21				
Chlorine															
A	<5	5.7 ± 1.9	3.7 ± 0.5	5.3 ± 1.3	10 ^a	<5 ^a	10 ^a	5 ^a	4.3 ± 0.5	10 ^a	6.7 ± 2.4				
B	<5	4.7 ± 1.3	5 ± 2.0	4.3 ± 0.9	-	-	-	-	3.7 ± 0.5	5 ^a	10.0 ± 7.1				
C	<5	5.0 ± 0.8	3.7 ± 0.9	3.7 ± 0.5	-	-	-	-	4.0 ± 0.8	5 ^a	5.0 ± 0.0				
X	5	4	5	6	-	-	-	-	7	10	10				
Y	4	5	6	4	-	-	-	-	7	10	10				
Z	11 ± 1	8	8	15	10 ^a	5 ^a	15 ^a	10 ^a	13 ± 2	10	13.5 ± 1.5				

^aDensities analysis of aggregated powders

Table 13. Summary of IC Analyses of Marble from the North Carolina Site for Anions, Annual and Multiyear Exposures (Layers A and U-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Third Annuals 1987-88		Triennials 1984-87		Quadrennial 1984-88	
Sulfate						
A	30.0 ±	1.6	23.3 ±	2.1	27.0 ±	3.6
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	36.3 ±	12.5	44.5 ±	4.5
Y	-	-	82.3 ±	8.2	85 ±	5
Z	1367 ±	5 ^a	4231 ±	663	4290 ±	1230
Nitrate						
A	<17	-	16.3 ±	1.3	<26	-
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	28.7 ±	5.3	34.3 ±	5.3
Y	-	-	32.7 ±	4.2	36.0 ±	8.0
Z	75 ±	16	131 ±	2	68.7 ±	14.6
Fluorine						
A	<8	-	<2	-	<8	-
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	<2	-	<8	-
Y	-	-	<3	-	<8	-
Z	11.3 ±	0.5	29 ±	12	26.3 ±	9.1
Chlorine						
A	<10	-	<5	-	<9	-
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	6.3 ±	1.7	8.7 ±	1.0
Y	-	-	6 ±	0	<9	-
Z	10 ±	0	17 ±	2	10 ±	1.6

Table 14. Summary of IC Analyses of Marble from the New Jersey Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate samples)

Anion, Layer	1984 - 1985 Quarterly				Annual		Biennial
	1	2	3	4	First	Second	1984-86
Sulfate							
A	<27.5	33.7 $\pm$ 1.7	32.3 $\pm$ 0.5	21.0 $\pm$ 2.9	16.7 $\pm$ 1.7	25 ^a	36.7 $\pm$ 4.7
B	<15	<15	<10	14.3 $\pm$ 0.5	<10.0	<20 ^a	<20.0
C	<15	<15	<10	14.0 $\pm$ 2.2	<11	<20 ^a	<25
X	30	32	42	44	95	80	185
Y	35	50	74	83	135	145	300
Z	624	1185	1000	856	2731 $\pm$ 14	2030	2881 $\pm$ 2059
Nitrate							
A	<15	<15	28.0 $\pm$ 4.3	17.0 $\pm$ 2.2	14.0 $\pm$ 1.4	<15 ^a	<22
B	<15	<15	13.3 $\pm$ 0.5	<10	11.7 $\pm$ 2.4	<15 ^a	<15
C	<15	<15	<14	<10	<9	<15 ^a	<15
X	18	<15	27	28	29	30	22
Y	17	<15	31	31	32	45	25
Z	48	55	99	104	95 $\pm$ 1	70	95
Fluorine							
A	<10	<5	<2	<2	2.7 $\pm$ 0.5	<5 ^a	<5
B	<10	<5	<2	<2	2.7 $\pm$ 0.5	<5 ^a	<5
C	<10	<5	<2	<2	2.7 $\pm$ 0.5	<5 ^a	<5
X	2	2	<2	<2	2	<5	<5
Y	2	2	<2	<2	1	<5	<5
Z	3	3	4	2	8.0 $\pm$ 1	10	15
Chlorine							
A	<5	<4	8.7 $\pm$ 0.9	<5	4.3 $\pm$ 0.5	5 ^a	8.3 $\pm$ 2.4
B	<5	<5	5.3 $\pm$ 0.5	4.0 $\pm$ 0.0	4.7 $\pm$ 0.9	5 ^a	5.0 $\pm$ 0.0
C	<5	<3	5.0 $\pm$ 0.8	4.3 $\pm$ 0.9	4.0 $\pm$ 0.0	5 ^a	<5
X	5	2	10	22	7	10	10
Y	5	2	12	6	7	15	10
Z	9	9	29	11	15.5 $\pm$ 0.5	10	15

^aDenotes analysis of aggregated powders.

Table 15. Summary of IC Analyses of Marble from the New York Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate samples)

Anion, Layer	1984 - 1985 Quarterly				Annual		Biennial
	1	2	3	4	First	Second	1984-86
Sulfate							
A	<15	<16	21.7 $\pm$ 2.1	<18	9.7 $\pm$ 0.9	<20 ^a	<32.5
B	<15	<15	<10	<12	<9	<20 ^a	<20
C	<15	<15	<10	<10	<9	<20 ^a	<20
X	16	<15	27	26	13	<20	<20
Y	18	16	32	30	13	<20	20
Z	275	381	418	169	515	80	1342
Nitrate							
A	<15	<15	<10	14.0 $\pm$ 1.4	<9	<15 ^a	<15
B	<15	<15	<10	<10	<9	<15 ^a	<15
C	<15	<15	<10	<10	<9	<15 ^a	<15
X	<12	<15	16	<10	<9	<15	<15
Y	<12	<15	16	<10	<9	<15	<15
Z	26	<15	45	18	<9	<15	20
Fluorine							
A	<5	<5	<2	<2	2.7 $\pm$ 0.5	<5 ^a	<5
B	<5	<5	<2	<2	2.7 $\pm$ 0.5	<5 ^a	<5
C	<5	<5	<2	<2	2.3 $\pm$ 0.5	<5 ^a	<5
X	<2	2	<2	<2	1	<5	<5
Y	2	2	<2	<2	1	<5	<5
Z	2	3	<2	<2	2	<5	<5
Chlorine							
A	<12	<3.5	<4	<3.5	3.3 $\pm$ 0.5	5 ^a	6.7 $\pm$ 2.4
B	<5	<3.5	3.3 $\pm$ 0.5	<3	3.7 $\pm$ 0.3	5 ^a	6.7 $\pm$ 2.4
C	<5	<4.5	3.3 $\pm$ 0.5	<3	4.3 $\pm$ 1.3	10 ^a	<5
X	3	2	8	4	7	5	5
Y	10	2	8	6	5	5	5
Z	8	3	11	6	4	5	10

^aDenotes analysis of aggregated powders.

Sulfate accumulation in the Z layers of briquettes exposed in the movable rack was of the same magnitude as in normally exposed stones. There is, however, a rather large difference between the sulfate concentration of the A and Z layers of the dry-regime briquettes. This phenomenon might be explained by the upward motion of warm, humid air from the ground, which lessens sulfate formation on the partially sheltered skyward surface. Concentrations of other measured anions follow the same pattern as the sulfate, but the values are much smaller.

Baseline IC analyses of preexposed limestone and marble demonstrate a different trend in anion accumulation over a prolonged exposure period, as shown in Fig. 6 for sulfate in limestone. The limestone briquettes were fabricated from slabs exposed vertically for 80 yr in a building being demolished in DC. Marble briquettes were cut from slabs exposed vertically for 20 yr in a stairwell at the Empire State Plaza Building in Albany, NY. Figure 6 shows that even though a slight rinsing effect by rain is evident in the outermost (A) layer, sulfate accumulation drops off slowly going inward from layer A, and even one-third through the total thickness the accumulation is still appreciable. The preexposed marble briquettes show a similar trend, but the concentration is several orders of magnitude smaller, probably due to the much shorter exposure period and partial protection of the marble slabs in the stairwell.

In both preexposed materials, the exposed surfaces were perpendicular to the horizontal, whereas the fresh stone briquettes were exposed 30° to the horizontal. Rinsing of these surfaces by impinging rain will affect the materials differently, as will the rain intensity and drying pattern between rain events. This may partially account for the differences in sulfate accumulation between fresh and preexposed stones. Analyses of exposed preexposed briquettes will hopefully yield a more qualitative answer to long-period exposure. The thickness of the shaved layers that were used to obtain the results shown in Fig. 6 varied from 10 to 50 mil, as indicated in the layer designation. Preexposed marble was analyzed only to a depth of 60 mil from the outermost pre-exposed surface. Variation in the concentration of other anions with depth follows the same pattern as sulfate, but is orders of magnitude lower. Cation concentrations, as analyzed by ICP, show that the concentration of magnesium is highest in both limestone and marble, as is evident from Tables 22 and 23. The concentration of other metallic elements is an order of magnitude or more lower. Magnesium levels are slightly higher in limestone than in marble, whereas the cation levels of the other elements differ little between the two stone types. The variation in magnesium concentration is small, if any, in the A layer and appears to decrease slightly as a function of exposure time, in the Z layer. The difference in magnesium concentration between A and Z layers appears to be very slight (less than 10%), and there appears to be an insignificant difference in the amounts of magnesium exposed at different sites. Similar trends are observed for the other cations, but the amounts are one or more magnitudes lower. These findings led to suspension of the ICP tests after the biennial exposure period.

Table 16. Summary of IC Analyses of Marble from the New York Site for Anions, Annual and Multiyear Exposures (Layers A and U-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given or analyses of replicate sample)

Anion. Layer	Third Annual 1987-88		Triennial 1984-87		Quadrennial 1984-88	
Sulfate						
A	20.3 $\pm$	0.5	15.7 $\pm$	1.7	21.3 $\pm$	1.3
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	-	-	-	-
Y	-	-	-	-	-	-
Z	745 $\pm$	29	2568 $\pm$	1168	3055 $\pm$	25
Nitrate						
A	<17	-	10 $\pm$	0.8	<17	-
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	-	-	-	-
Y	-	-	-	-	-	-
Z	<18	-	25 $\pm$	2	40 $\pm$	12
Fluorine						
A	<8	-	<2	-	<8	-
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	-	-	-	-
Y	-	-	-	-	-	-
Z	<8	-	4 $\pm$	0	<8	-
Chlorine						
A	<9	-	8.3 $\pm$	0.9	14.3 $\pm$	0.9
U	-	-	-	-	-	-
V	-	-	-	-	-	-
W	-	-	-	-	-	-
X	-	-	-	-	-	-
Y	-	-	-	-	-	-
Z	14.3 $\pm$	3.1	6 $\pm$	1	19.5 $\pm$	1.5

Fig. 6.

Sulfate concentration through total thickness of preexposed limestone

LAYER DESIGNATION

Layer	1(A)	0-10 mil	Layer	12	480-500 mil
	2(B)	10-20 mil		14	720-760 mil
	3(C)	20-30 mil		16	1480-1520 mil
	8(F)	50-60 mil		18(X)	1970-1980 mil
	8	90-100 mil		19(Y)	1980-1990 mil
	10	240-260 mil		20(Z)	1990-2000 mil

Table 17. Summary of IC Analyses of Marble from the Washington, DC, Site for Anions, Quarterly, Annual, and Biennial Exposures (Layers A-C and X-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Quarterly																Annual		Biennial
	1984-85				1987-88												First	Second	
	1	2	3	4	13	14	15	16											
Sulfate																			
A	30.0 ± 0.0	29.0 ± 4.2	25.7 ± 3.4	41.3 ± 4.2	41.3 ± 2.1	37.8 ± 1.9	69.3 ± 9.0	-									44.0 ± 15.8	55 ^a	40.0 ± 0.0
B	<15	<15	10.3 ± 0.5	14.0 ± 1.6	-	-	-	-	-	-	-	-	-	-	-	-	11.3 ± 0.5	25 ^a	<20
C	<15	<15	<17	<16	-	-	-	-	-	-	-	-	-	-	-	-	10.7 ± 0.5	95	200
X	30	42	33	28	-	-	-	-	-	-	-	-	-	-	-	-	90	115	315
Y	42	35	38	46	-	-	-	-	-	-	-	-	-	-	-	-	107	1545	4560 ± 15
Z	450	999	356	462	427 ± 65	870 ± 50	562 ± 99	662 ± 97									2132 ± 87		
Nitrate																			
A	<17	<19	<19	14.0 ± 1.4	<10	<10	28.5 ± 6.5	-									12.3 ± 0.5	35 ^a	18.3 ± 2.4
B	<17	<15	<11	<10	-	-	-	-	-	-	-	-	-	-	-	-	<17	35 ^a	<15
C	<15	<15	<12	<10	-	-	-	-	-	-	-	-	-	-	-	-	16	<15	20
X	30	17	18	25	-	-	-	-	-	-	-	-	-	-	-	-	18	30	30
Y	31	25	21	28	-	-	-	-	-	-	-	-	-	-	-	-	18	75	135 ± 4.5
Z	100	86	69	70	40 ± 8	57.3 ± 13.8	141 ± 6	153 ± 18									51 ± 1		
Fluorine																			
A	<5	<5	<2	<2	<9	<9	<10	-									2.7 ± 0.5	<5 ^a	<5
B	<5	<5	<2	<2	-	-	-	-	-	-	-	-	-	-	-	-	2.3 ± 0.5	<5 ^a	<5
C	<5	<5	<2	<2	-	-	-	-	-	-	-	-	-	-	-	-	2.0 ± 0.0	<5 ^a	<5
X	2	4	<2	<2	-	-	-	-	-	-	-	-	-	-	-	-	1	<5	<5
Y	2	2	<2	<2	-	-	<10	<7									16 ± 2	10	38 ± 2
Z	5	6	4	4	<19	<9	<10	<7											
Chlorine																			
A	5.0 ± 0.0	11.0 ± 5.0	5.0 ± 2.2	4.3 ± 0.5	15 ± 2.2	<10	<15	-									4.3 ± 0.5	5 ^a	6.7 ± 2.4
B	<5	4.3 ± 0.5	<4	3.3 ± 0.5	-	-	-	-	-	-	-	-	-	-	-	-	3.7 ± 0.5	<5 ^a	<5
C	<5	6.7 ± 3.3	3.7 ± 0.5	<4	-	-	-	-	-	-	-	-	-	-	-	-	3.3 ± 0.5	<5 ^a	<5
X	11	9	6	6	-	-	-	-	-	-	-	-	-	-	-	-	6	5	10
Y	11	10	7	6	-	-	-	-	-	-	-	-	-	-	-	-	5	<5	10
Z	24	41	11	10	<10	28.3 ± 4.5	18.7 ± 2.5	28.3 ± 2.9									11 ± 3	10	18 ± 3

^aDenotes analysis of aggregated powders.

Table 18. Summary of IC Analyses of Marble from the Washington, DC, Site for Anions, Third Annual, 1987-88 ; Triennial, 1984-87; and Quadrennial, 1984-88 (Layers A and U-Z, $\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion. Layer	Third Annuals 1987-88	Triennials 1984-87	Quadrennial 1984-88
Sulfate			
A	33.7 $\pm$ 3.9	76.7 $\pm$ 6.2	31.7 $\pm$ 4.5
U	-	-	-
V	-	-	-
W	-	-	-
X	-	207 $\pm$ 33	-
Y	-	285 $\pm$ 44	-
Z	1447 $\pm$ 118	5842 $\pm$ 485	7700 $\pm$ 1683
Nitrate			
A	<29	46.7 $\pm$ 2.4	<18.5
U	-	-	-
V	-	-	-
W	-	-	-
X	-	25.0 $\pm$ 4.1	-
Y	-	33.3 $\pm$ 2.4	-
Z	<78 $\pm$ 16	170 $\pm$ 7.1	150 $\pm$ 28
Fluorine			
A	<7	<2	<10
U	-	-	-
V	-	-	-
W	-	-	-
X	-	<2	-
Y	-	<2	-
Z	24.7 $\pm$ 0.5	50 $\pm$ 4.1	71 $\pm$ 21
Chlorine			
A	15.7 $\pm$ 0.5	20 $\pm$ 4.1	15.7 $\pm$ 1.9
U	-	-	-
V	-	-	-
W	-	-	-
X	-	11.7 $\pm$ 2.4	-
Y	-	18.3 $\pm$ 2.4	-
Z	19.7 $\pm$ 2.1	28.3 $\pm$ 2.4	22 $\pm$ 5.7

Table 19. Summary of IC Analyses of Marble from the Ohio Site for Anions, Quarterly, Annual, and Biennial Exposures ($\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate samples)

Anion. Layer	Quarterly								Annual		Biennial	
	9	10	11	12	1986-87	1987-88	1988-89	1989-90	1986-87 First	1987-88 Second	1986-87	1988-89
Sulfate												
A	117 $\pm$ 14	143 $\pm$ 6.8	78.5 $\pm$ 8.5	208 $\pm$ 45	225 $\pm$ 30	73.7 $\pm$ 6.6	88.5 $\pm$ 0.5					
B	-	-	-	-	-	-	-					
C	-	-	-	-	-	-	-					
X	-	-	-	-	-	-	-					
Y	-	-	-	-	-	-	-					
Z	1385 $\pm$ 200	2167 $\pm$ 90	1106 $\pm$ 16	1427 $\pm$ 134	2970 $\pm$ 355	2663 $\pm$ 373	4827 $\pm$ 562					
Nitrate												
A	11.3 $\pm$ 0.5	26.3 $\pm$ 5.3	13.5 $\pm$ 1.5	15 $\pm$ 0.0	15 $\pm$ 0.0	<24	<17					
B	-	-	-	-	-	-	-					
C	-	-	-	-	-	-	-					
X	-	-	-	-	-	-	-					
Y	-	-	-	-	-	-	-					
Z	30.7 $\pm$ 0.9	36.7 $\pm$ 3.3	34.5 $\pm$ 3.5	40 $\pm$ 0.0	50 $\pm$ 4.1	35.7 $\pm$ 6.2	43.3 $\pm$ 5.7					
Fluorine												
A	<2	<2	<2	<2	<2	<7	<7					
B	-	-	-	-	-	-	-					
C	-	-	-	-	-	-	-					
X	-	-	-	-	-	-	-					
Y	-	-	-	-	-	-	-					
Z	6.7 $\pm$ 0.9	6.7 $\pm$ 0.0	8.5 $\pm$ 0.5	10 $\pm$ 0.0	30 $\pm$ 4.1	23.7 $\pm$ 3.1	45.7 $\pm$ 2.9					
Chlorine												
A	<6.5	15.0 $\pm$ 7.8	5.5 $\pm$ 0.5	15 $\pm$ 4.1	20 $\pm$ 4.1	11.7 $\pm$ 1.9	13.7 $\pm$ 0.5					
B	-	-	-	-	-	-	-					
C	-	-	-	-	-	-	-					
X	-	-	-	-	-	-	-					
Y	-	-	-	-	-	-	-					
Z	12.3 $\pm$ 4.7	15.3 $\pm$ 2.1	11.0 $\pm$ 2.0	15 $\pm$ 4.1	13.3 $\pm$ 2.4	12.3 $\pm$ 1.3	15.3 $\pm$ 1.3					

Table 20. Summary of IC Analyses of Marble from the Movable Rack at Ohio Site for Anions, 1987-88 ($\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate sample)

Anion, Layer	Dry Regime		Sprayed Regime	
Sulfate				
A	808	$\pm$ 83	408	$\pm$ 151
U	-		-	
V	-		-	
W	-		-	
X	-		-	
Y	-		-	
Z	3025	$\pm$ 415	2720	$\pm$ 260
Nitrate				
A	55	$\pm$ 12	67	$\pm$ 1
U	-		-	
V	-		-	
W	-		-	
X	-		-	
Y	-		-	
Z	70	$\pm$ 0	60	$\pm$ 16
Fluorine				
A	9.5	$\pm$ 0.5	9	$\pm$ 0
U	-		-	
V	-		-	
W	-		-	
X	-		-	
Y	-		-	
Z	21.5	$\pm$ 1.5	25	$\pm$ 2
Chlorine				
A	24	$\pm$ 4	31	$\pm$ 5
U	-		-	
V	-		-	
W	-		-	
X	-		-	
Y	-		-	
Z	27.5	$\pm$ 0.5	17.5	$\pm$ 3.5

The surface chemistry analyses show that sulfate formation is the predominant chemical change occurring on limestone and marble surfaces. The skyward surface is rinsed by rain periodically, and gypsum accumulation is rather small, forming mostly in dry periods between rainfalls. The measured concentration is an average obtained from a layer 0.25-mm-thick, whereas the thickness of the actual gypsum layer is only 100 to 250 μm . The groundward layer, sheltered from rain events, shows a sulfate concentration proportional to the exposure time and the SO_2 content of the ambient atmosphere. Whereas fresh limestone exhibits sharp sulfate concentration gradients going inward from the groundward surface, pre-exposed limestone shows a more gradual gradient, penetrating deeper into the stone. This indicates qualitatively that surface inclination with respect to rain and wind direction plays a role in the chemical process of sulfate formation. The gypsum buildup in rain-sheltered areas leads ultimately to spallation, as seen on older structures and monuments. This phenomenon has not yet occurred in the test briquettes. The high level of sulfate in the groundward layer, and the low level in the skyward layer indicate that airborne SO_2 is dry-deposited between rain events and reacts with the carbonate in the specimens. During rain events, the sulfate in the skyward layer is washed away.

Table 21. Summary of IC Analyses of Pre-Exposed Stone Control Samples for Anions, ($\mu\text{g/g}$; Average $\pm$ standard deviation given for analyses of replicate samples)

Layer and Thickness, mil	Limestone				Marble			
	Sulfate	Nitrate	Fluorine	Chlorine	Sulfate	Nitrate	Fluorine	Chlorine
1 (A) 0-10 3 (d) 20-30	21150 $\pm$ 1550	49 $\pm$ 9	71.7 $\pm$ 7.3	35.7 $\pm$ 8.6	136	24.7 $\pm$ 11.9	<5	49 $\pm$ 39
6 50-60	23633 $\pm$ 3793	50 $\pm$ 5	47 $\pm$ 0.8	41.3 $\pm$ 9.3	172 $\pm$ 36	19 $\pm$ 7.8	<5	31 $\pm$ 19
8 90-100	10350 $\pm$ 250	30 $\pm$ 7	34.3 $\pm$ 3.3	36.3 $\pm$ 4.0	152 $\pm$ 48	19.3 $\pm$ 7.8	<5	34 $\pm$ 18
10 240-260	3505 $\pm$ 425	27 $\pm$ 1	26.7 $\pm$ 5.3	33 $\pm$ 2.5	-	-	-	-
12 480-500	2450 $\pm$ 143	44 $\pm$ 4	<11	34 $\pm$ 2.2	-	-	-	-
14 720-760	1375 $\pm$ 85	22 $\pm$ 1.3	<10	34 $\pm$ 4.1	-	-	-	-
16 1480-1520	1009 $\pm$ 149	21.3 $\pm$ 1.3	<10	31 $\pm$ 2.9	-	-	-	-
20 (Z) 1990-2000	182 $\pm$ 48	<17	<10	28 $\pm$ 6.2	-	-	-	-
	232 $\pm$ 45	<17	<10	30 $\pm$ 1.4	-	-	-	-

A rough quantitative estimate of recession per rain event can be made, assuming that each rain event completely rinses away the sulfate accumulation in the skyward (A) layer. Accumulation of measured sulfate in this layer occurred between the last rain event and removal of the briquettes from the exposure site before shaving and analysis. The amount of sulfate per unit area is equal to the product of briquette density, layer thickness (0.25 mm), and the measured sulfate concentration in the A layer. This sulfate accumulation is the reaction product of the stone material and airborne SO_2 . The amount of reacted carbonate per unit area equals the ratio of the density of the stone material to the density of sulfate, multiplied by the amount of sulfate formed per unit area. Recession per rain event can then be calculated from the ratio of the reacted carbonate to the weight of a 1- μm -thick layer of stone material. This approach leads to the following expressions:

- For marble, Recession (in μm) per rain event = $2.596 \times 10^{-4} \times (\text{sulfate concentration in } \mu\text{g/g})$.
- For limestone, Recession (in μm) per rain event = $2.212 \times 10^{-4} \times (\text{sulfate concentration in } \mu\text{g/g})$.

Implementation of these formulae, using an average annual sulfate concentration in Layer A and the following densities:

2.7 g/cm^3 for marble,
2.3 g/cm^3 for limestone,
2.6 g/cm^3 for calcium sulfate,

yields the results shown in Table 26.

Table 22. Summary of ICP Analyses of Salem Limestone for Cations^a (µg/g; Average ± standard deviation given for analyses of replicate samples)

Source	Exposure Period, Layer	Mg	Al	Mn	Ba	Cr	Cu	Fe	Sr	Zn
Control Briquettes	A	2720 ± 54	29.7 ± 0.7	67.7 ± 1.9	<5	<5	7.0 ± 2.2	243 ± 21	210 ± 0	9.3 ± 1.3
	B	2740 ± 30	31.3 ± 4.7	63.0 ± 2.2	<5	<5	6.7 ± 1.7	247 ± 31	207 ± 5	8.0 ± 0.8
	C	2703 ± 19	36.0 ± 5.4	63.3 ± 2.5	<5	<5	5.0 ± 1.4	253 ± 33	210 ± 0	7.7 ± 0.5
NC	First Quarter									
	A	2740 ± 108	<33.0 ± 10.2	69.3 ± 3.9	<10	<5	9.7 ± 4.7	233 ± 40	210 ± 0	10.3 ± 2.1
	B	2677 ± 82	28.3 ± 1.3	66.3 ± 2.6	<5	<5	5.0 ± 1.4	227 ± 25	210 ± 1.3	8.7 ± 1.3
Annual	A	2740 ± 104	23.0 ± 2.5	66.0 ± 2.2	<5	<5	7.0 ± 2.5	230 ± 22	207 ± 5	8.3 ± 0.5
	B	2760 ± 82	60.7 ± 4.1	69.3 ± 4.2	<5	6.7 ± 0.5	7.3 ± 0.5	270 ± 0	223 ± 5	10.3 ± 0.5
	C	2730 ± 14	39.3 ± 2.5	61.3 ± 1.9	<5	6.7 ± 0.5	<5	250 ± 8	220 ± 0	8.0 ± 0.0
NJ	First Quarter									
	A	2747 ± 87	31.3 ± 9.0	65.0 ± 4.6	<13	<5	8.7 ± 6.6	250 ± 22	193 ± 25	13.0 ± 2.2
	B	2713 ± 37	28.0 ± 1.4	59.7 ± 2.1	<10	<5	4.0 ± 0.8	230 ± 16	210 ± 0	8.3 ± 0.5
Biennial	A	2727 ± 31	23.3 ± 2.4	58.0 ± 2.2	9.7 ± 1.3	<5	3.7 ± 0.9	217 ± 19	213 ± 5	7.7 ± 0.5
	B	2620 ± 41	87.0 ± 0.8	66.3 ± 2.9	<5	<5	2.3 ± 0.5	423 ± 126	213 ± 5	26.3 ± 0.9
	C	2480 ± 20	<20	62	6	<5	3	370	220	10
NY	First Quarter									
	A	2753 ± 31	25.0 ± 4.1	63.3 ± 7.4	<8	<5	5.3 ± 1.3	227 ± 17	207 ± 10	9.7 ± 0.5
	B	2737 ± 53	23.0 ± 3.0	60.7 ± 3.3	<12	<5	0.3 ± 2.4	220 ± 16	203 ± 17	9.3 ± 0.9
Biennial	A	2737 ± 47	25.0 ± 5.7	59.3 ± 2.5	<15	<5	6.3 ± 2.1	223 ± 21	203 ± 5	8.0 ± 1.4
	B	2643 ± 31	68.7 ± 19.6	67.0 ± 2.8	<5	<5	<2	353 ± 38	220 ± 0	13.0 ± 1.6
	C	2490 ± 40	40	69	<5	<5	<2	280	230	6
DC	First Quarter									
	A	2647 ± 61	43.3 ± 1.9	64.3 ± 2.1	<5	5.3 ± 0.5	7.0 ± 2.2	247 ± 21	217 ± 21	13.0 ± 0.8
	B	2630 ± 28	32.3 ± 3.1	60.3 ± 1.7	<5	5.0 ± 0.0	7.3 ± 2.6	220 ± 14	217 ± 5	9.7 ± 0.5
Biennial	A	2657 ± 58	27.7 ± 3.1	58.7 ± 1.0	<5	5.7 ± 0.5	6.3 ± 1.9	213 ± 17	217 ± 5	8.3 ± 0.5
	B	2600 ± 38	94.7 ± 4.1	61.3 ± 1.3	<5	<5	3.0 ± 0.0	373 ± 21	210 ± 0	21 ± 0
	C	2400 ± 31	31	57	6	<5	3	410	230	10

^aCd, De, Ni, Pb, Co, V were also analyzed, and results were consistently below detection.

Table 23. Summary of ICP Analyses of Shelburne Marble for Cations^a (µg/g: Average ± standard deviation given for analyses of replicate samples)

Source	Exposure Period, Layer	Mg	Al	Mn	Ba	Cr	Cu	Fe	Sr	Zn
Control Briquettes	A	1850 ± 514	55.3 ± 38.8	17.7 ± 0.5	<5	<5	7.3 ± 1.7	300 ± 37	160 ± 8	<3
	B	1823 ± 501	45.7 ± 30.0	17.7 ± 0.5	<5	<5	7.0 ± 1.4	290 ± 28	157 ± 5	<3
	C	1763 ± 419	38.3 ± 16.7	17.3 ± 0.5	<5	<5	6.7 ± 1.9	290 ± 30	157 ± 5	<3
NC	First Quarter									
	A	1513 ± 70	<22	18.0 ± 0.0	<5	<5	7.3 ± 1.7	317 ± 53	157 ± 13	3.0 ± 0.8
	B	1503 ± 74	<22	17.3 ± 0.5	<5	<5	4.3 ± 0.5	287 ± 25	157 ± 13	<2
Annual	C	1503 ± 67	<22	17.3 ± 0.5	<5	<5	5.0 ± 1.7	270 ± 8	153 ± 17	<2
	A	2098 ± 160	66.7 ± 29.5	19.0 ± 1.4	<5	<5	<5	320 ± 121	187 ± 25	<3
	B	2050 ± 151	67.7 ± 35.6	18.7 ± 1.7	<5	<5	<5	343 ± 175	190 ± 30	<3
X	C	2077 ± 172	59.7 ± 39.0	18.7 ± 1.7	<5	<5	<5	353 ± 182	187 ± 25	<2
	X	2960 ± 192	192 ± 69.7	20 ± 1.7	<5	<5	<5	480 ± 160	180 ± 25	<2
	Y	2790 ± 152	152 ± 64	20 ± 1.7	<5	<5	<5	400 ± 150	150 ± 25	<2
	Z	2850 ± 164	164 ± 64	21 ± 1.7	<5	<5	<5	440 ± 160	160 ± 25	<2
Biennial	A	1537 ± 141	<20	18.0 ± 0.0	<5	<5	<2	243 ± 34	151 ± 16	<2
	Z	2320 ± 98	98 ± 38	10 ± 1.7	<5	<5	<2	250 ± 34	182 ± 25	<2
NJ	First Quarter									
	A	2077 ± 745	<60	18.3 ± 0.9	<5	<5	6.3 ± 2.6	253 ± 10	160 ± 14	3.3 ± 1.3
	B	2123 ± 792	<63	18.3 ± 0.9	<5	<5	6.3 ± 2.6	253 ± 10	160 ± 14	<3
Biennial	C	2063 ± 749	<64	18.3 ± 0.9	<5	<5	6.3 ± 2.6	253 ± 5	160 ± 14	<3
	A	2017 ± 313	<57	17.0 ± 0.8	<5	<5	<8	343 ± 114	156 ± 6	8.3 ± 9.0
	Z	1690 ± 16	<20	16 ± 1.7	<5	<5	<2	270 ± 153	153 ± 2	2
NY	First Quarter									
	A	1697 ± 216	26.7 ± 2.4	17.3 ± 1.3	<5	<5	7.3 ± 1.9	273 ± 31	170 ± 14	3.3 ± 0.5
	B	1720 ± 265	28.3 ± 3.7	17.3 ± 1.3	<5	<5	7.3 ± 1.3	273 ± 31	170 ± 14	<3
Biennial	C	1720 ± 249	27.0 ± 5.0	17.3 ± 1.3	<5	<5	7.3 ± 1.9	270 ± 36	170 ± 14	<3
	A	1697 ± 305	<20	16.3 ± 0.5	<5	<5	<2	300 ± 22	155 ± 10	<3
	Z	1240 ± 15	<20	15 ± 1.7	<5	<5	<2	236 ± 160	160 ± 2	<2
DC	First Quarter									
	A	1497 ± 78	<20	17.7 ± 0.5	<5	<5	5.7 ± 2.4	273 ± 33	163 ± 13	<3
	B	1487 ± 74	<20	17.3 ± 0.5	<5	<5	5.3 ± 1.9	270 ± 30	163 ± 13	<2
Biennial	C	1493 ± 82	<20	17.0 ± 0.0	<5	<5	4.3 ± 1.9	270 ± 30	163 ± 13	<2
	A	1507 ± 264	<26	16.7 ± 0.5	<5	<5	<4	267 ± 24	145 ± 11	3.7 ± 1.7
	Z	3550 ± 90	90 ± 38	17 ± 1.7	<5	<5	2	290 ± 163	163 ± 2	2

^aCd, Be, Ni, Pb, Co, V were also analyzed, and results were consistently below detection.

Table 24. Average Annual Aerometric Data

Site	Temp. °C	Rain, mm	H+ Conc. mg/L	Ph
NC	15.0	900	57.91	4.26
NJ	9.9	1225	65.92	4.21
NY	5.0	1006	54.35	4.28
DC	14.6	765	89.81	4.17
OH	12.0	839	137.16	4.05

Table 25. Linear Regression Line Equations

Material, Site	Equation			Correlation Coefficient
Marble				
NC	C^b	= 1228	$t^c + 337$	.97
NJ	C	= 1388	$t + 449$	.93
NY	C	= 774	$t - 71$	.97
DC	C	= 1950	$t + 68$	.995
OH	C	= 2218	$t + 502$	.98
Limestone ^a				
NC	C	= 5335	$t + 1402$	.95
NJ	C	= 6938	$t + 2056$	.95
NY	C	= 1481	$t + 224$	.91
DC	C	= 9477	$t + 2187$	.98
OH	C	= 13986	$t + 2642$	.985

Table 26. Average Recession due to Sulfate Dissolution, per Rain Event (μm)

Site	Marble/ event	Limestone/ event
NC	0.0056	0.0137
NJ	0.0049	0.0171
NY	0.0041	0.0135
DC	0.0108	0.0419
OH	0.0387	0.0953

The data in the table are slightly below the values obtained by Reddy (8) from runoff experiments. To compare these data with recession measurements obtained by gravimetry, the values of Table 26 must be multiplied by the number of rain events per year. In the above estimates, rain intensity, temperature, and time between the last rain event and briquette removal were not considered. Prorated yearly, recession values obtained from gravimetry are generally higher than those obtained from runoff measurements, which suggests that other processes contribute to material losses in the exposed briquettes. Additional data will contribute to a more accurate statistical evaluation of the chemical processes, help formulate a dose-response function, and –it is hoped– explain high sulfate accumulation deep in the limestone exposed for 80 yr.

ACKNOWLEDGMENTS

The author thanks the many people who assisted with and cooperated in this investigation. In particular, the author thanks NPS Project Officer Susan I. Sherwood for her encouragement, valuable support, and advice. Thanks also go to field site operators Curtis Moore (NC), Paul Fiechter (NJ), Raymond Masters (NY), NPS personnel (DC), and B. Weber (OH), all of whom assisted in briquette installation, exchange, and removal; Frank Bittles (ANL) for briquette fabrication and shaving; Florence Smith (ANL) for chemical, IC, and ICP analyses; and C. Arthur Youngdahl for initiating and diligently guiding this program from 1984 through 1987. The assistance and participation of numerous other people in producing this report is greatly appreciated.

REFERENCES

1. *National Acid Precipitation Assessment Program Annual Report to the President and Congress*, U.S. Government Printing Office, Washington, DC (1985).
2. S. I. Sherwood, The National Park Service Program on the Effects of Air Pollution on Cultural Properties, 77th Ann. Air Pollution Control Assn. Conf., San Francisco (June 1984).
3. B. R. Doe, Ed., *Acid Rain Site Management Plan for Dimension Stone*, U.S. National Park Service, Preservation Assistance Division, Washington, DC (1984).
4. C. A. Youngdahl and B. R. Doe, Effects of Atmospheric Exposure on Roughening, Recession, and Chemical Alteration of Marble and Limestone Sample Surfaces in the Eastern United States, in *Materials Degradation Caused by Acid Rain*, pp. 266-284, ACS Symposium Series 318, R. Babolian, Ed., American Chemical Society, Washington, DC (1986).
5. C. Arthur Youngdahl and Bruce R. Doe, Dimensional, Chemical, and Gravimetric Changes in Marble and Limestone Exposed at Field Test Sites of the National Acid Precipitation Assessment Program, in *Materials Effects Task Group VII Peer Review Summaries*, pp. 215-225, North Carolina State University Acid Deposition Program, Raleigh (1986).
6. M. Ross and L. Knab, *Selection, Procurement, and Description of Salem Limestone Samples Used to Study Effects of Acid Rain*, NBSIR 84-2905, National Bureau of Standards, Gaithersburg, MD (1984).
7. M. Ross, *Description, Selection, and Procurement of Shelburne Marble Used to Study Effects of Acid Rain*, USGS Open-File Report 85-594, U. S. Geological Survey, Reston, VA (1985).
8. M. M. Reddy, personal communication.

APPENDIX A:

Stone Surface Sampling Procedure

and

Summary of Sampling and Analytical Report

STONE SURFACE SAMPLING PROCEDURE
AND
SUMMARY OF SAMPLING AND ANALYTICAL REPORT

I. PROCEDURE

Samples of stone surfaces containing chemical alteration products are taken from briquettes by means of a Hendy shaper, a highly adjustable, automatic, and precise machine. The machinist, after thoroughly cleaning the shaper prior to use, installs a briquette, as shown in Fig. A.1. and with the aid of a dial gage carefully establishes a level position on the surface to be sampled. The machine is then adjusted, a specially designed metal pan is installed as a receiver of stone sample powder beneath the briquette, and the horizontally reciprocating motion of the tungsten carbide tool bit is initiated to remove the first layer of sample from the briquette. When this procedure of removal, hereinafter called shaving, is completed, the resulting powder is brushed from the briquette into the pan and from the pan into a clean glass sample bottle, which is then capped and labeled. The succeeding layers are shaven in a similar manne. Any powder samples not specified for analysis are archived.

Fig. A1. Stone Specimen Mounted in Shaping Machine for Surface Sampling. Tungsten carbide tool bit, reciprocating horizontally, precisely shaves a layer of stone from the specimen, producing powder for chemical analysis

APPENDIX B:

Specifications of Field Procedures

from Site Management Plan

SPECIFICATIONS OF FIELD PROCEDURES

FROM SITE MANAGEMENT PLAN

The briquette selection plan is outlined in Chapter V of Ref. 3. Presented below is the detailed briquette-handling protocol for field exposure sites, as it appears in Ref. 3.

A. Introduction

Briquette specimens of dimension stone are being tested under outdoor exposure conditions at sites that are instrumented to record air quality, precipitation chemistry, and weather data. The exposure effects on the specimens are analyzed periodically by NAPAP investigators. Changes in surface chemical composition, physical properties, weight, and color are monitored. For most of the measurements, the briquette samples are shipped to participating laboratories. Some specimens are returned to field sites for further exposure. Because the rate of damage caused by acid rain and weathering is small, very sensitive methods of analysis are employed. This protocol is written for exposure site personnel participating in the work to inform them of the need for great care in sample handling and to specify procedures to insure the program's success. A separate protocol was provided for sample-processing personnel in laboratories.

A drawing of the standard briquette sample is given in Fig. 1 of the text. The upper face (3-1/4 x 2-15/16 in.) of the briquette was given a standard surface finish before the initial exposure in the field, and this surface is the one of greatest interest to investigators. It is to face generally skyward during exposure in its sample rack, except that the plane of the upper surface of the briquette is purposely inclined 30° to the horizontal by the slope of the rack; that is, the back edge of the briquette's upper surface is somewhat higher than the front edge when the sample is in the rack. The identification code of the sample has been marked on the front surface with an arrow pointing toward the standard (upper) surface. The front and back surfaces are not parallel to each other: the taper is present to help avoid possible dislodging of the sample by high winds (see Sample Installation, below). During handling, the sample should be gripped (with the use of rubber or vinyl gloves) at the side surfaces, which are parallel to each other (Fig. 1). All surfaces of each briquette are of some interest to investigators; therefore, care should be taken to avoid contamination, disturbance of any deposits, and physical damage to any surface, edge, or corner of briquettes during handling.

B. Withdrawal of Briquettes From Racks, Wrapping, and Shipping

1. Samples should be handled with great care. Clean rubber or vinyl gloves should be worn by site personnel to contact the samples, and only side surfaces should be gripped. No firm contact with the upper surface of samples should be made (see Introduction), and no contamination of any sample surface during handling should be allowed.

2. The briquettes must be allowed to dry naturally in the racks before removal. When the briquettes are damp on the date of a scheduled withdrawal, removals should be deferred by one day if humidity is not high (<50%) and longer if humidity is high (>50%). When it is very high, conditions are inappropriate for removals. The effect of dew in contributing moisture to briquettes should be included in decisions on sufficient dryness: morning removal would not

be favorable if dew had affected the briquettes overnight. This caution is to avoid loss of microgram quantities of surface product from the stone samples, e.g., to the interior surface of the Ziploc bags, prior to analysis.

Removal of samples should not be done in haste or under difficult or hazardous conditions. If any such conditions are present on the date of a scheduled withdrawal, the withdrawal may be delayed slightly at the discretion of site personnel.

3. Plan and prepare indoors for the work completely before beginning withdrawals. Consult the schedule provided for identities of samples to be removed, and locate their rack positions from the placement chart provided. Gather all Ziploc bags (1/briquette), bubble wrap (2/briquette), rubber bands (3/briquette), and clean gloves needed. Consult Steps 5c-e. If color-change/weight-change samples are to be withdrawn, bag and wrap the six unexposed briquettes that are stored inside the test station. Remove excess wrappers from the foam-padded, reusable shipping container provided (retaining extra wrappers that may be needed to fill void space after loading samples), place materials needed (and six wrapped samples if applicable) in the container, and take it along with the notes, a roll of strapping tape, and scissors to the rack site.

4. Arrange to remove the specified briquette without disturbing other briquettes or contaminating them with any substance. Samples in the top two rows of the rack may have to be reached from behind the rack with the use of a step-platform or other stable support. Convenience should be established so that care in treatment of samples is facilitated.

5. Remove one of the specified samples and wrap it as follows: (a) while wearing rubber or vinyl gloves, turn the plastic screw of the specified location in the rack at least three full turns in the direction that increases the gap width for removal of the tapered briquette; (b) move the briquette upslope and clear of its Plexiglass support pegs and only then lift it away from its support rods and gently out of the rack, taking care not to scrape the pegs or screw head against the sample during removal; (c) place the briquette in a clean Ziploc bag, expel excess air, and seal the bag; (d) wrap one 12-in. x 12-in. sheet of bubble wrap around the sample, fasten with one rubber band, wrap a similar sheet of the bubble plastic over the first, secure with two crossed rubber bands, and place the wrapped sample in the padded shipping container; and (e) record any pertinent observations, including notes on mistakes or accidents that may have affected the briquettes.

6. Repeat the foregoing procedure for the remaining samples of the set specified, one sample at a time.

7. Fill remaining space in the container with additional sheets of bubble wrap, and close and latch the container.

8. Apply strapping tape to insure that the container does not come apart while being carried or in shipping.

9. Ship the container, marked "Fragile," via expeditious ground transportation (for example, UPS Ground) to the address indicated on the schedule provided. (Air shipment must be avoided because partial depressurization may alter fluid distribution in the porous samples and may disturb any surface deposits or residues.)

C. Handling of Briquettes Received at Field Sites

The foregoing procedure should be consulted for guidance in sample handling.

1. On receipt of a shipping container of briquettes from a participating laboratory, the container should be handled carefully and stored indoors in an area not subject to flooding or

extreme ambient conditions until a time appropriate for placement of samples into exposure racks. Placement should not be done in haste, during inclement weather, or under difficult or hazardous conditions.

2. Plan and prepare indoors for the work completely before unpacking the container. Consult the schedule provided for identities of samples to be placed and for their assigned locations. If there are questions, phone Susan Sherwood, NPS, FTS or area code 202-343-1055.

3. If weight-change/color-change samples are received, open the container indoors and locate the six briquettes that are used for monitoring effects of handling and shipping. These samples, which are not to be exposed to weathering, will be found labeled on the outside sheet of bubble wrap around each sample. With the use of clean rubber or vinyl gloves, unwrap these six briquettes and place the briquettes carefully on a protected, flat, indoor surface. Record pertinent information and observations.

4. If the container was opened (see Step 3), close and latch the shipping container, re-apply strapping tape, and transport the container and notes to the outdoor rack location.

5. Open the container, remove one briquette, and remove bubble wrap. Note sample identity and assigned location in rack. Arrange a means of convenient access to the assigned location without disturbance of other briquettes on the rack. With the use of clean rubber or vinyl gloves, remove the briquette from the Ziploc bag, gripping the sample at the side surfaces only, and place in the assigned location with care to avoid chipping edges or scraping surfaces on supporting pins or screw head of rack compartment. The label on the briquette should be facing the downslope direction of the rack, and the arrow of the label should be pointing generally skyward. While avoiding contact with the briquette's upper surface, manually turn the plastic screw of the compartment until a 1/32-in. gap remains between screw and briquette. Record any pertinent remarks.

6. Remove the next briquette from the shipping container and repeat the foregoing procedure of unwrapping and placement. Repeat until all briquettes are properly installed and recorded.

7. Place bags, bubble wrap, and rubber bands in the shipping container and store the container in a dry location indoors until next use.

APPENDIX C:

Protocols for IC and ICP Analyses

PROTOCOLS FOR IC AND ICP ANALYSES

The protocols for IC and ICP analyses, prepared by personnel of the Analytical Chemistry Laboratory, Chemical Technology Division of ANL, are reproduced in this appendix verbatim, except for the modification of the designations of internal appendices as necessary to avoid ambiguity in this report.

Revised Protocol for

The Determination of Cations and Anions on Marble/Limestone Surfaces

Sampling: Sampling is the responsibility of the submitter. It is expected that 1-2 gm samples of powdered material obtained by milling surface material from limestone and marble samples will be provided for analysis.

Cation Analysis: Cations to be analyzed include cadmium, zinc, lead, vanadium, and manganese. Other metals, such as aluminum, strontium, and magnesium can be determined simultaneously using an inductively coupled plasma-atomic emission spectrometer (ICP-AES). Ammonium ion, NH_4^+ cannot be analyzed by ICP-AES. It can be determined by a variety of other methods. The protocol described includes dissolution of the sample. This analysis will include metals from the matrix as well as absorbed species. A sampled layer from well below the exposed surface will serve as the matrix reference. The difference in metal concentration observed between surface sample and matrix sample will be a measure of absorbed cation. This approach assumes that the metals analyzed are homogeneously distributed in the sample.

Procedure:

1. Weigh 0.5 g sample to the nearest milligram.
2. Transfer the sample to a carefully cleaned, dry 2 oz. plastic screw-cap bottle.
3. Add 2.0 mL of 15 M HNO_3 (Baker Instru. Analyzed).
4. Add 5 mL deionized H_2O and shake to disintegrate sample.
5. Add 43 mL deionized H_2O to yield a solution containing 10 mg sample/mL in 0.3-0.4 M HNO_3 .
6. Mix well, allow the solution to settle and determine analyte concentrations by inductively coupled plasma-atomic absorption spectrometry (see Note 2).
7. Calculate analyte concentration:

$$\text{ppm Analyte} = \frac{\text{micrograms/mL} \times 50}{\text{S.Wt.,g}}$$

Anion Analysis:

Anions including F^- , Cl^- , NO_3^- , and SO_4^{2-} are analyzed by Ion Chromatography (IC) after leaching a weighed sample with a known volume of dilute Na_2CO_3 - NaHCO_3 solution.

Procedure:

1. Weigh a 0.5 g sample to the nearest milligram. Transfer to a clean, dry, 2-oz plastic screw-cap bottle.
2. Add 25 mL of 0.003 M NaHCO_3 -0.0025 M Na_2CO_3 solution and mix thoroughly.
3. Let stand overnight.
4. Determine the concentrations of anions in solution by ion chromatography (see Note 3).

Discussion Regarding Detection Limits and Precision

Precision and accuracy for ICP-AES measurements are a function of the concentration of analyte measured. Detection limits* for elements of concern have been measured in water solution to be:

<u>Element</u>	<u>Detection Limit, $\mu\text{g/mL}$</u>
Cd	0.002
Zn	0.001
Pb	0.020
V	0.001
Mn	0.0004
Al	0.010
Sr	0.0002
Mg	0.0004

The relative precision of analyte measurements at detection limit concentrations is $\pm 50\%$. At higher concentrations, the specifications of our instrument require that the ICP-AES system shall be capable of determining the elements listed above as a minimum with a precision of $\pm 10\%$ (for ten (10) consecutive determinations) when element concentrations are equal to ten (10) times the listed detection limits; with a precision of $\pm 10\%$ [or ten (10) consecutive determinations] when element concentrations are equal to ten (10) times the listed detection limits; with a precision of $\pm 3\%$ for concentrations equal to or greater than one hundred (100) times the specified detection limits. Our instrument performs to the specification.

The data in Table C.1 indicate the estimated concentrations of metal (at varying precision levels) that can be determined in marble/limestone samples using the protocol described herein.

Table C.1

Element	Detections Limit (DL)*			10 x DL			100 x DL		
Cd	0.2	$\pm$	50% Relative	2.0	$\pm$	10% Relative	20.0	$\pm$	3% Relative
Zn	0.10	$\pm$	50% Relative	1.0	$\pm$	10% Relative	10.0	$\pm$	3% Relative
Pb	2.0	$\pm$	50% Relative	20.0	$\pm$	10% Relative	200	$\pm$	3% Relative
V	0.10	$\pm$	50% Relative	1.00	$\pm$	10% Relative	10.0	$\pm$	3% Relative
Mn	0.04	$\pm$	50% Relative	0.40	$\pm$	10% Relative	4.00	$\pm$	3% Relative
Al	1.0	$\pm$	50% Relative	10.0	$\pm$	10% Relative	10.0	$\pm$	3% Relative
Sr	0.02	$\pm$	50% Relative	0.20	$\pm$	10% Relative	2.00	$\pm$	3% Relative
MG	0.04	$\pm$	50% Relative	0.40	$\pm$	10% Relative	4.00	$\pm$	3% Relative

*ppm in solid samples.

*Detection Limit (DL) specified as follows: The analyte concentration that corresponds to a net analyte signal three (3) times the standard deviation of the background noise. The standard deviation background is determined from ten (10) consecutive measurements, each integration not exceeding ten (10) seconds.

Data calculated assuming 0.5 g marble/limestone sample dissolved in acid and diluted to 50.0 mL. ICP-AES measurements made on dissolved sample solution.

The relative precision of the determinations made using the Ion Chromatograph is estimated to be $\pm 5\%$.

1. Clean plastic bottles by rinsing with deionized water and air dry.
2. Details for analysis of metals by ICP-AES are given in the attached Quality Assurance Document No. C-0030-0303, "Current Standard Operating Procedures for the Determination of Total Metals in Water by Inductively Coupled Plasma-Atomic Emission Spectrometry (ICP-AES)."
3. Determination of anions by ion chromatography.

A. Equipment

1. Dionex model 14 Ion Chromatograph upgraded to Model 16 setup for anion analysis with:
 - (a) 3 x 150 mm fast run anion pre-column.
 - (b) 3 x 500 mm fast run anion separator.
 - (c) Anion fiber suppressor.
2. Honeywell, dual pen recorder.
3. Millipore, 0.22- μ m disposable filter.
4. 10-mL disposable plastic syringe.

B. Reagents

1. Deionized water is used in all operations.
2. Eluant - .0025 M Na_2CO_3 -9.0003 M NaHCO_3 .
3. Dilute Standards.
 - (a) #1-0.05 ppm F^- , 0.10 ppm Cl^- , 1.00 ppm NO_3^- , 1.00 ppm SO_4^{2-} .
 - (b) #2-0.25 ppm F^- , 0.50 ppm Cl^- , 5.00 ppm NO_3^- , 5.00 ppm SO_4^{2-} .
 - (c) #3-0.50 ppm F^- , 1.00 ppm Cl^- , 10.00 ppm NO_3^- , 10.00 ppm SO_4^{2-} .
4. Blind Standard Solution - A standard prepared by the quality control representative and treated as an unknown sample by the analyst.

C. Anion Determinations

1. Instrument operating conditions.
 - (a) System column toggle is set in the independent position.
 - (b) Meter is set on 3 μ ho Full Scale.
 - (c) Recorder chart speed - slow, 0.5 cm/min.
 - (d) Pump flow rate set for 2.5 mL/min.
2. Suppressor regeneration - the anion fiber suppressor has a constant reverse flow regenerate (0.025 NH_2SO_4) over the fiber which provides continuous regeneration of the suppressor during operation.
3. Instrument Startup
 - (a) Power and air supply toggle switches are turned on.

- (b) The anion pump is turned on. The regenerate solution is turned on and the eluant is placed on line. The system is stabilized when a steady baseline is achieved. This should take no more than 15 minutes. If a stable baseline is not achieved, see Dionex Manual, TROUBLESHOOTING, pp. 83-84.

4. Sample Analysis

- (a) Inject dilute standard #1 and obtain a chromatogram.
- (b) Repeat Step 4a for dilute standards #2 and #3.
- (c) Check the retention times for the anions and measure peak heights. (Typical retention times are: F^- - 1.6 min, Cl^- - 2.8 min, NO_3^- - 7.2 min, and SO_4^{2-} - 8.8 min.)
- (d) Inject four samples and one blind standard until all samples are analyzed.
- (e) Check retention times to determine which anions are present. Measure the height of each peak.
- (f) Repeat the analysis of dilute standards #1, #2, and #3.
- (g) Average the peak heights due to each ion in each standard chromatogram obtained before and after sample analysis.
- (h) Plot average peak heights versus concentration ($\mu g/mL$) for each anion.
- (i) Determine the concentration of each ion in the sample leach solution from the curve generated in Step 4h above.
- (j) Calculate ppm of analyte anion in the sample.

$$\text{ppm Analyte Anion in Sample} = \frac{\text{mg Anion} / \text{mL in Leach} \times 25}{\text{Sample Weight, g}}$$

APPENDIX D:

Results of IC and ICP Analyses

Standard Operating Procedure
Using Ion Chromatography for the Determination of
Inorganic Anions in Marble and Limestone Samples

Quality Assurance
SOP: ACL-139

Analytical Chemistry Laboratory
Chemical Technology Division
Argonne National Laboratory

June 29, 1989
(Date of Original Issue)

Prepared by: Florence P. Smith

	For	Date
Reviewed: <u>J. J. Martins</u> ACL QA/QC Coordinator	CMT/ACL	<u>8/24/89</u>
Approved: <u>Donald G. Tracy</u> ACL Group Leader	CMT/ACL	<u>8/24/89</u>

Argonne National Laboratory/Analytical Chemistry Laboratory
Standard Operating Procedure: Using Ion Chromatography for the
Determination of Inorganic Anions in Marble and Limestone Samples

1. Scope and Application

- 1.1 This procedure covers the determination of inorganic anions (i.e., F^- , Cl^- , NO_3^- , and SO_4^{2-}) in aqueous solutions prepared by leaching marble or limestone powders with a weak carbonate buffer solution.
- 1.2 The ion chromatographic measurement procedure is also applicable to determination of the anions listed above in other aqueous samples.
- 1.3 This procedure should be used by or under the supervision of an analyst experienced in the use of ion chromatography (IC), the operation of the instrument, and the interpretation of the resulting chromatogram.

2. Summary of the Procedure

- 2.1 Samples, each consisting of 1 to 2 g of powdered material obtained by milling surface material from a marble or limestone test briquette, are provided by the requestor. A weighed portion of the sample is leached in a sodium carbonate-bicarbonate solution. A volume of the leachate is injected into an ion chromatograph. An aliquot may be diluted if necessary. The ions are separated and measured using a system comprised of a guard column, separator column, suppressor column, and conductivity detector. Identification of the anions is made by retention times. Quantification is accomplished by comparing peak responses of unknown solutions to those of standard solutions.

3. Definitions

- 3.1 Stock standard solution – a concentrated solution containing a known analyte standard. The stock standard solution is used to prepare a secondary standard solution.
- 3.2 Calibration standards (CS) – a solution of mixed analytes prepared in the laboratory from secondary standard solutions.
- 3.3 Quality control sample (QCS) – a solution containing known concentrations of analytes and used to demonstrate that acceptable identifications and measurements can be obtained with this procedure. Suitable QCS may be obtained from either the National Institute of Standards and Technology or the Environmental Protection Agency.
- 3.4 The instrument detection limit (IDL) is defined as the minimum concentration of an anion that can be measured and reported with 99% confidence that the value is above zero. The solution IDL concentrations listed in Table 1 were

obtained using reagent water; corresponding IDL concentrations, in the limestone or marble solid, were calculated from each solution IDL using the nominal sample weight and leachate volume specified for sample preparation.

Table 1. Chromatographic Conditions and Instrument Detection Limits in Reagent Water^a

Analyte	Retention Time ^b (Minutes)	Relative Retention Time	Solution IDL ^c , mg/L	Solid IDL ^c , mg/kg
Fluoride	0.85	1.00	0.002	0.16
Chloride	1.28	1.50	0.010	0.80
Nitrate-N	2.64	3.10	0.003	0.24
Sulfate	4.68	5.50	0.037	3.0

^aOperating Conditions:

Columns – HPIC-AG4A Guard; HPIC-AS4A Separator; Anion micromembrane suppressor

Conductivity Detector – Dionex, 1.5 μ L volume

Eluant – 0.0030M NaHCO₃-0.0022M Na₂CO₃

Sample Loop – 100 μ L

Flow Rate – 2.00 mL/min

^bConcentration of mixed standard (mg/L) 0.050 F⁻, 0.05 Cl⁻, 0.10 NO₃⁻, 0.10 SO₄⁻²

^cInstrument Detection Limit (IDL) calculated from data obtained using an attenuator setting of 0.3 μ MHO full scale. Other settings would produce an IDL proportional to their value.

4. Interferences

- 4.1 Interferences can be caused by ions with retention times that are similar to and overlap those anions of interest. High concentrations of an anion can interfere with the peak resolution of an adjacent ion. Sample dilution and/or spiking can be used to solve these problems. Eluant concentration can be adjusted to improve resolution between peaks.
- 4.2 The “water dip,” a negative peak that elutes near and can interfere with the fluoride and chloride peaks, can be eliminated by making the solution being analyzed to contain the same concentration of eluant as contained in the blank; e.g., X mL of sample plus 1.00 mL of 100X concentrated eluant (6.2.1) diluted to 100 mL.
- 4.3 Interferences may be caused by contaminants in the reagents, glassware, etc. Blanks should be analyzed to determine the level of any such contamination and corrective actions taken to eliminate the problem.
- 4.4 Particles larger than 0.20 microns in reagents and 0.45 microns in samples must be filtered out prior to analysis.

- 4.5 Weak organic acids (formic, acetic, etc.) can coelute with the anions of interest. Sodium tetraborate eluant is used to eliminate interferences of this type.
- 4.6 Inorganic ions (I^- , SCN^- , etc.) that strongly adhere to the separator can result in loss of resolution. A 0.1M Na_2CO_3 solution can be used to remove them from the separator.

5. Apparatus and Materials

- 5.1 Balance – analytical, capable of accurately weighing to the nearest 0.0001 g.
- 5.2 Ion Chromatograph with analytical columns, detector, autosampler, and micro-processor, Dionex Model 4340i, or equivalent.
 - 5.2.1 Anion guard column: AG4A-Dionex P/N 037042 or equivalent.
 - 5.2.2 Anion separator column: AS4A-Dionex P/N 037041 or equivalent.
 - 5.2.3 Anion micromembrane suppressor: AMMS-1, Dionex P/N 038019 or equivalent.
 - 5.2.4 Detector-conductivity cell: 1.5 mL volume, Dionex or equivalent.
 - 5.2.5 Hewlett-Packard 9133/HP310 computer and all required accessories.
 - 5.2.6 Autosampler, Dionex or equivalent.
 - 5.2.7 Sample vials and cap with filters.
- 5.3 Filters: 0.22 mm, disposable.
- 5.4 Syringes, polyethylene, disposable.
- 5.5 Volumetric flasks.
- 5.6 Pipettes.

6. Reagents and Standards

- 6.1 Reagent water – distilled or deionized water, which meets ASTM Type I requirements.
- 6.2 Eluant solution.
 - 6.2.1 0.30M $NaHCO_3$ -0.22M Na_2CO_3 – Dissolve 50.41 g $NaHCO_3$ and 46.64 g Na_2CO_3 in reagent water and dilute to 2 L.
 - 6.2.2 Sodium Bicarbonate 0.0030M-Sodium Carbonate 0.0022M – Dilute

20.00 mL of 0.30M NaHCO_3 -0.22M Na_2CO_3 solution (6.2.1) with reagent water to 2 L.

6.2.3 Sodium Tetraborate 0.070M – Dissolve 26.70 g of $\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$ in reagent water and dilute to 1 L.

6.3 Regeneration solution-Sulfuric Acid 0.025N – Dilute 2.8 mL conc. sulfuric acid (H_2SO_4) to 4 L with reagent water.

6.4 Stock standard solutions, 1000 mg/L (1 mg/mL) – Stock standard solutions may be purchased as certified solutions or prepared from ACS reagent grade salts (dried at 105°C for 1 hr) as listed below:

6.4.1 Chloride (Cl^-) 1000 mg/L – Dissolve 1.6500 g sodium chloride (NaCl) in reagent water and dilute to 1 L.

6.4.2 Fluoride (F^-) 1000 mg/L – Dissolve 2.2100 g sodium fluoride (NaF) in reagent water and dilute to 1 L.

6.4.3 Nitrate (NO_3^-) 1000 mg/L – Dissolve 1.3715 g sodium nitrate (NaNO_3) in reagent water and dilute to 1 L.

6.4.4 Sulfate (SO_4^{2-}) 1000 mg/L – Dissolve 1.8140 g potassium sulfate (K_2SO_4) in reagent water and dilute to 1 L.

7. Calibration and Standardization

7.1 Establish ion chromatographic operating parameters equivalent to those in Table 1.

7.2 Prepare calibration standards (containing all of the anions of interest at a minimum of three concentration levels) and a blank by accurately measuring volumes from the secondary standard solutions into a volumetric flask and diluting to volume with reagent water. A sufficient number of standards must be analyzed to allow an accurate calibration curve to be established. One of the standards should be representative of a concentration near, but above, the instrument detection limit (IDL). The other standards should correspond to the range of concentrations expected in the sample and should define the working range of the detector. Unless the attenuator range settings are proven to be linear, each setting must be calibrated individually.

7.3 Using injections of 0.01 to 1.0 mL (determined by injection loop volumes) of each calibration standard, tabulate peak height against the concentration. Prepare a calibration curve for each analyte using the results of the foregoing measurements. Retention times must be recorded; retention time is inversely related to the concentration. The correlation coefficient should be 0.995 or greater. If not, prepare new standards and repeat.

- 7.4 The calibration curve must be verified on each working day or whenever the eluant is changed. If the retention time for any analyte varies from the expected values (Table 1) by more than $\pm 10\%$, the calibration must be repeated. If the retention-time difference is still more than $\pm 10\%$, a new set of calibration standards must be prepared.
- 7.5 Nonlinear response can result when the separator-column capacity is exceeded (overloading). Maximum column loading (all anions) should not exceed about 100 ppm.

8. Sample Preparation

- 8.1 Sampling is the responsibility of the submitter. Approximately 1 to 2 grams of powder obtained by milling surface material from a limestone or marble test briquette is required for analysis.
- 8.2 Weigh approximately 0.25 gram of sample into a clean, dry scintillation screw-cap vial. Add 20.00 mL of 0.0030M NaHCO_3 -0.0022M Na_2CO_3 solution and mix thoroughly. Let stand overnight. Filter a portion of the resulting leachate into a sample vial.

9. Quality Control

- 9.1 Analyze a quality control sample (QCS) containing all the anions of interest for the initial calibration verification (ICV). If any measured value falls more than $\pm 10\%$ from the true value, the analysis must be terminated, the problem identified and corrected, and the ICV analysis repeated. If the ICV results are within the acceptance range, sample analysis may begin.
- 9.2 Analyze a laboratory blank to demonstrate that all glassware, materials, and reagents are under control. Each time there is a change in any of the aforementioned items, a laboratory blank must be processed.
- 9.3 For continuing calibration verification (CCV), analyze the QCS at a frequency of 10%. If a CCV result is not within $\pm 10\%$ of the expected value, terminate the analysis. Identify and correct the problem and reanalyze all samples analyzed since the previous acceptable CCV.

10. Analysis of Samples and Operation of the Instrument

- 10.1 Using the computer "main menu" program, develop and record a report title, a method, and a schedule. An established method and typical schedule are included for guidance (Attachment 1).

NOTE: Fluoride results must be verified using sodium tetraborate (7% of a 0.070M solution and 93% of reagent water) as eluant. These determinations are

made using a gradient elution to permit the removal of other anions from the columns. A typical gradient program is also included in Attachment 1.

- 10.2 Following the schedule established in Section 10.1, load the autosampler with the standard and sample vials. The vials must be in correct sequence, e.g., vial No. 1 contains standard No. 1, etc.

- 10.2.1 The standards must include a blank and QCS.

- 10.2.2 Set the keypads on the autosampler to the following position: local, run, loop, prop, off, 1.

- 10.3 Set all modules of the IC [(e.g., advanced chromatography module (CMA), gradient pump (GPM), conductivity detector (CDM)] to the remote position.

- 10.4 Using the computer "main menu" page 1, select the "execute" program.

- 10.5 Press softkey 2 "load CIM," page 1. The screen will clear to read "download the CIM."

- 10.5.1 Answer all computer "prompts" with the necessary information. The screen will return to page 1 of the execute program.

- 10.6 Press softkey 3 "start." The screen will clear to page 2 of the start program. Answer prompts with the necessary information. The screen will return to page 1 of the execute program and the analysis will begin.

- 10.7 When all standards and samples are analyzed, the "halt" program will shut the instrument down. See Attachment 2 for a typical halt method.

11. Calculations and Report of Results

- 11.1 The HP310 computer calculates the concentration ($\mu\text{g/mL}$ or $\mu\text{g/g}$) found in the standard and the samples, using the parameters generated in the "method program," Section 10.1.

- 11.2 Report sample results in $\mu\text{g/g}$.

- 11.3 Report all results on the Report of Analytical Results, Form CMT-84 (10-84), Attachment 3.

12. Maintenance and Troubleshooting

- 12.1 For routine maintenance on the Dionex 4340i system, see the pertinent subsection of the "Operator's Manual."

- 12.2 For maintenance on the computer system, see "The Auto Ion 300 Software" manual.

- 12.3 For troubleshooting on any component of the Dionex 4340i system, see the subsection of the "Operator's Manual."
- 12.4 For troubleshooting on the computer system, see "The Auto Ion 300 Software" manual.

13. References

- 13.1 "The Determination of Inorganic Anions in Water by Ion Chromatography," Method 300.0, James W. O'Dell, John D. Pfaff, Morris E. Gales, and Gerald D. McKee, EPA-6/4-84-017, March 1984.
- 13.2 "Dionex Series 4000i Operator's Manual," Dionex Corporation, Sunnyvale, CA.
- 13.3 Auto Ion 300 Chromatography Software for the HP310 Training and Reference Manual, Dionex Corporation, Sunnyvale, CA.
- 13.4 "Dionex Basic Ion Chromatography Training Course Manual," Dionex Corporation, Sunnyvale, CA.

ATTACHMENT 1

Method Name: ANION
Date : 11/16/88
Operator : FPS

METHOD PARAMETERS

Detector Parameters

1 or 2 detectors ? (1 OR 2).....	1.00
The detector is a CDM (0) or not a CDM (1)	0.00

Graphics Parameters

Run time (minutes).....	7.00
End time for plot (minutes).....	7.00
Initial delay time (minutes).....	0.00
# of CRT pages for real time plot (1 to 99)	1.00
Full scale for plot of detector 1 (CDM=uS;others=mV)....	10.00
# of CRT pages for replot (0 TO 99)	1.00
Vertical scale factor for replot (units of largest peak)	1.00
Offset for the replot ? (mV or uS)	0.00
Put component names on the replot? (0=no, 1=yes).....	1.00

Report Parameters

Printer select code.....	717.00
Print result report (0=no, 1=yes).....	1.00
List components not found in sample? (0=no, 1=yes).....	1.00
Include unknown peaks in report ? (0=no, 1=yes).....	1.00
Record raw data ? (0=no, 1=yes).....	1.00
Record result data ? (0=no, 1=yes).....	0.00
Link to user program ? (0=no, 1=yes).....	0.00

Integration Parameters

Sampling rate (seconds).....	.20
Peak threshold (mV or uS/data pt interval).....	.05
Starting peak width (seconds).....	10.00
Peak area reject (microvolt-sec).....	200.00

Calibration Parameters

Internal or external standard ? (0=external, 1=internal)	0.00
Quantitate peaks by height (1) or area (0).....	1.00
Update response factors by replacement(0) or average (1)	0.00
Number of calibration levels (1 TO 6).....	4.00
Fit type for multilevel cal.(0=p to p,1=linear,2=quadratic)	1.00
Default sample volume injected.....	1.00
Default dilution factor.....	1.00
Total numbers of components ? (0 to 50)	5.00
Area reject for ref. peaks ?.....	500.00
% ret. time window for reference peaks.....	5.00
Ref. peak ret. time window (sec).....	15.00

RAW DATA FILE :

Response factor for unknowns = 1.0000E-04

Component Units= ppm

1 FLUORIDE Ret.Time= 1.05 min.
 Ref. peak: CHLORIDE Window size: 5%
 Least squares slope = 7.0288E-04 Least squares Intercept = 5.7904E-02

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	118	1.200000E-01	1.0127253E-03
2	251	2.400000E-01	9.5557669E-04
3	797	6.400000E-01	8.0303296E-04
4	2601	1.880000E+00	7.2272517E-04

2 CHLORIDE Ret.Time= 1.55 min.
 Ref. peak: CHLORIDE Window size: 5%
 Least squares slope = 9.7953E-04 Least squares Intercept = -8.9576E-03

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	113	1.100000E-01	9.7070782E-04
2	235	2.200000E-01	9.3451414E-04
3	631	6.000000E-01	9.5100269E-04
4	1905	1.860000E+00	9.7625842E-04

3 NITRATE-N Ret.Time= 3.39 min.
 Ref. peak: CHLORIDE Window size: 5%
 Least squares slope = 7.0120E-04 Least squares Intercept = -1.9036E-02

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	170	1.100000E-01	6.4553038E-04
2	344	2.200000E-01	6.3899152E-04
3	690	4.500000E-01	6.5236034E-04
4	1243	8.600000E-01	6.9189927E-04

4 PHOSPHATE-P Ret.Time= 4.05 min.
 Ref. peak: CHLORIDE Window size: 5%
 Least squares slope = 3.4578E-03 Least squares Intercept = 6.1762E-02

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	38	1.600000E-01	4.2472138E-03
2	70	3.300000E-01	4.7457819E-03
3	166	6.500000E-01	3.9106855E-03
4	320	1.160000E+00	3.6217113E-03

5 SULFATE Ret.Time= 5.74 min.
 Ref. peak: CHLORIDE Window size: 5%
 Least squares slope = 3.2628E-03 Least squares Intercept = 9.5113E-03

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	76	2.510000E-01	3.2856475E-03
2	150	5.020000E-01	3.3498570E-03
3	610	2.010000E+00	3.2947293E-03
4	1053	3.440000E+00	3.2664739E-03

IC controls in file : ANCON

EVENT#	TIME	CIM EVENT DISCPT.	EVENT CODE
1	0.0	LOAD	L

2	0.0	C.CELL ON		CC
3	0.0	C.RANGE=	10.0	CR.1-CR10000
4	0.0	A OFF		-A
5	0.0	B OFF		-B
6	0.0	HOLD GPM		HO
7	0.0	AC1 ON		AC1
8	0.0	C.TMP COMP	1.7	TC0-TC9.9
9	.1	RLY1 ON		RL1
10	2.5	C.OFFSET 0		CO
11	2.7	ST SAMPLIN		S
12	2.7	INJECT		I
13	3.5	RLY1 OFF		-RL1
14	5.0	LOAD		L

Gradient program in file; GPMANCON

ISOCRATIC ANION ANALYSIS

0.0027MNaHCO₃-0.0020MNa₂CO₃

HI limit: 1800

LO limit: 0

#	Time	Flow	%1	%2	%3	%4	5	6
1	0.0	2.0	100.0					

Method Name: ANGRAD
Date : 01/30/89
Operator : FPS

METHOD PARAMETERS

Detector Parameters

1 or 2 detectors ? (1 OR 2).....	1.00
The detector is a CDM (0) or not a CDM (1)	0.00

Graphics Parameters

Run time (minutes).....	5.00
End time for plot (minutes).....	5.00
Initial delay time (minutes).....	1.75
# of CRT pages for real time plot (1 to 99)	1.00
Full scale for plot of detector 1 (CDM=uS;others=mV)....	10.00
# of CRT pages for replot (0 TO 99)	1.00
Vertical scale factor for replot (units of largest peak)	1.00
Offset for the replot ? (mV or uS)	0.00
Put component names on the replot? (0=no, 1=yes).....	1.00

Report Parameters

Printer select code.....	717.00
Print result report (0=no, 1=yes).....	1.00
List components not found in sample? (0=no, 1=yes).....	1.00
Include unknown peaks in report ? (0=no, 1=yes).....	1.00
Record raw data ? (0=no, 1=yes).....	1.00

Record result data ? (0=no, 1=yes)..... 0.00
 Link to user program ? (0=no, 1=yes)..... 0.00

Integration Parameters

Sampling rate (seconds)..... .20
 Peak threshold (mV or uS/data pt interval)..... .05
 Starting peak width (seconds)..... 10.00
 Peak area reject (microvolt-sec)..... 250.00

Calibration Parameters

Internal or external standard ? (0=external, 1=internal) 0.00
 Quantitate peaks by height (1) or area (0)..... 1.00
 Update response factors by replacement(0) or average (1) 0.00
 Number of calibration levels (1 TO 6)..... 4.00
 Fit type for multilevel cal.(0=p to p, 1=linear, 2=quadratic) 1.00
 Default sample volume injected..... 1.00
 Default dilution factor..... 1.00
 Total numbers of components ? (0 to 50) 1.00
 Area reject for ref. peaks ?..... 250.00
 % ret. time window for reference peaks..... 10.00
 Ref. peak ret. time window (sec)..... 15.00

RAW DATA FILE :

Response factor for unknowns = 1.0000E-04

Component Units= ppm

1 FLUORIDE Ret.Time= 2.24 min.
 Ref. peak: FLUORIDE Window size: 10%
 Least squares slope = 4.9646E-04 Least squares Intercept = 5.8252E-02

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	181	1.200000E-01	6.6368382E-04
2	391	2.400000E-01	6.1410235E-04
3	1065	6.400000E-01	6.0076660E-04
4	3695	1.880000E+00	5.0882405E-04

INDEX TIME DATA REDUCTION EVENTS

1 5.89 10 Start peak detection

IC controls in file : ORGAN

EVENT#	TIME	CIM EVENT DISCPT.	EVENT CODE
1	0.0	C.CELL ON	CC
2	0.0	C.RANGE= 10.0	CR.1-CR10000
3	0.0	A OFF	-A
4	0.0	B OFF	-B
5	0.0	HOLD GPM	HO
6	0.0	ACI ON	ACI
7	.1	RLY1 ON	RL1
8	2.6	C.OFFSET 0	CO

9	2.7	INJECT	I
10	2.7	RUN GPM	RU
11	2.7	ST SAMPLIN	S
12	4.0	RLY1 OFF	-RL1
13	5.0	LOAD	L

Gradient program in file; GPMORGAN

0.07(0.07MNa2B4O7)-.93(H2O)

0.29(0.07MNa2B4O7)-.71(H2O)

HI limit: 2500

LO limit: 0

#	Time	Flow	%1	%2	%3	%4	5	6
1	0.0	2.0		93.0		7.0		
2	3.5			93.0		7.0		
3	3.7			90.0		10.0		
4	5.0			93.0		7.0		

35 methods in this schedule, schedule recorded in file SCHED:,703

Sample_name	Method_file	Data_file	Volume injected	Int.std. conc.	Dilution factor
1 AUTOCAL1	ANGRAD	JULY20	1.00	1.0000	1.00
2 AUTOCAL2	ANGRAD	JULY20	1.00	1.0000	1.00
3 AUTOCAL3	ANGRAD	JULY20	1.00	1.0000	1.00
4 AUTOCAL4	ANGRAD	JULY20	1.00	1.0000	1.00
5 BLANK	ANGRAD	JULY20	1.00	1.0000	1.00
6 LCS-1	ANGRAD	JULY20	1.00	1.0000	1.00
7 89-0534-41	ANGRAD	JULY20	1.00	1.0000	80.35
8 89-0534-42	ANGRAD	JULY20	1.00	1.0000	77.97
9 89-0534-43	ANGRAD	JULY20	1.00	1.0000	80.94
10 89-0534-44	ANGRAD	JULY20	1.00	1.0000	78.89
11 89-0534-45	ANGRAD	JULY20	1.00	1.0000	80.71
12 89-0534-46	ANGRAD	JULY20	1.00	1.0000	79.77
13 BLANK	ANGRAD	JULY20	1.00	1.0000	1.00
14 LCS-2	ANGRAD	JULY20	1.00	1.0000	1.00
15 89-0534-47	ANGRAD	JULY20	1.00	1.0000	82.82
16 89-0534-48	ANGRAD	JULY20	1.00	1.0000	78.62
17 89-0534-49	ANGRAD	JULY20	1.00	1.0000	81.40
18 89-0534-50	ANGRAD	JULY20	1.00	1.0000	81.00
19 89-0534-51	ANGRAD	JULY20	1.00	1.0000	79.90
20 89-0534-52	ANGRAD	JULY20	1.00	1.0000	80.71
21 BLANK	ANGRAD	JULY20	1.00	1.0000	1.00
22 LCS-3	ANGRAD	JULY20	1.00	1.0000	1.00
23 89-0534-53	ANGRAD	JULY20	1.00	1.0000	80.45
24 89-0534-54	ANGRAD	JULY20	1.00	1.0000	81.43
25 89-0534-55	ANGRAD	JULY20	1.00	1.0000	78.62
26 89-0534-56	ANGRAD	JULY20	1.00	1.0000	79.05
27 89-0534-57	ANGRAD	JULY20	1.00	1.0000	80.71
28 89-0534-58	ANGRAD	JULY20	1.00	1.0000	78.93
29 BLANK	ANGRAD	JULY20	1.00	1.0000	1.00
30 LCS 4	ANGRAD	JULY20	1.00	1.0000	1.00
31 89-0534-59	ANGRAD	JULY20	1.00	1.0000	80.77
32 89-0534-60	ANGRAD	JULY20	1.00	1.0000	81.10
33 BLANK	ANGRAD	JULY20	1.00	1.0000	1.00
34 LCS-5	ANGRAD	JULY20	1.00	1.0000	1.00
35	HALT		1.00	1.0000	1.00

ATTACHMENT 2

Method Name: HALT
Date : 6/16/87
Operator : FPS

METHOD PARAMETERS

Detector Parameters

1 or 2 detectors ? (1 OR 2).....	1.00
The detector is a CDM (0) or not a CDM (1)	0.00

Graphics Parameters

Run time (minutes).....	.30
End time for plot (minutes).....	.30
Initial delay time (minutes).....	0.00
# of CRT pages for real time plot (1 to 99)	1.00
Full scale for plot of detector 1 (CDM=uS;others=mV)....	10.00
# of CRT pages for replot (0 TO 99)	1.00
Vertical scale factor for replot (units of largest peak)	1.00
Offset for the replot ? (mV or uS)	0.00
Put component names on the replot? (0=no, 1=yes).....	0.00

Report Parameters

Printer select code.....	717.00
Print result report (0=no, 1=yes).....	1.00
List components not found in sample? (0=no, 1=yes).....	0.00
Include unknown peaks in report ? (0=no, 1=yes).....	0.00
Record raw data ? (0=no, 1=yes).....	0.00
Record result data ? (0=no, 1=yes).....	0.00
Link to user program ? (0=no, 1=yes).....	0.00

Integration Parameters

Sampling rate (seconds).....	.20
Peak threshold (mV or uS/data pt interval).....	.05
Starting peak width (seconds).....	10.00
Peak area reject (microvolt-sec).....	1000.00

Calibration Parameters

Internal or external standard ? (0=external, 1=internal)	0.00
Quantitate peaks by height (1) or area (0).....	1.00
Update response factors by replacement(0) or average (1)	0.00
Number of calibration levels (1 TO 6).....	1.00
Default sample volume injected.....	1.00
Default dilution factor.....	1.00
Total numbers of components ? (0 to 50)	1.00
Area reject for ref. peaks ?.....	1000.00
% ret. time window for reference peaks.....	5.00
Ref. peak ret. time window (sec).....	30.00

Response factor for unknowns = 1.0000E-04

Component Units= ppm

1 FLUORIDE Ret.Time= .92 min.
 Ref. peak: FLUORIDE Window size: 5%

LEVEL	HEIGHT	CONCENTRATION	RATIO(CONC./HEIGHT)
1	0	2.700000E-01	1.000000E-04

IC controls in file : HALTTE

EVENT#	TIME	CIM EVENT DISCPT.	EVENT CODE
1	0.0	LOAD	L
2	0.0	HOLD GPM	HO
3	0.0	B OFF	-B
4	0.0	A OFF	-A
5	0.0	C.CELL OFF	-CC
6	0.0	C.OFFSET 0	-CO
7	0.0	RLY1 OFF	-RL1
8	0.0	AC1 OFF	-AC1
9	.1	RUN GPM	RU
10	.3	STOP GPM	-ST

Gradient program in file; GPMHALTTE

HI limit: 1800
 LO limit: 0

#	Time	Flow	%1	%2	%3	%4	5	6
1	0.0	2.0	100.0					

ATTACHMENT 3**ANALYTICAL CHEMISTRY LABORATORY**
Argonne National Laboratory
Argonne, IL 60439**REPORT OF ANALYTICAL RESULTS**

Sample Material:

Date Received:

Submitted by:

Date Reported:

Your Number	Our Number	

NOTE: Samples will be discarded one (1) month after date of report unless otherwise arranged. When making future inquiries regarding this work, you must reference **OUR** number(s) above. For further information about the results reported here, please call _____ at 2-_____.

Copies To:

Analyst(s):

Current Standard Operating Procedures for the
Determination of Total Metals in Water by
Inductively Coupled Plasma-Atomic
Emission Spectrometry (ICP-AES)

Quality Assurance

Document No. C-0030-0303

Argonne National Laboratory
Chemical Technology Division
Analytical Chemistry Laboratory

September 23, 1983
(Date of Original Issue)

Prepared by: E. A. Huff

	For	Date
Approved: R. Bane, ACL QA Coordinator	CMT/ACL	9/30/83
Reviewed: J. Geller, Project Quality Engineer	QAD	9/30/83
Reviewed: K. Jensen, ACL Group Leader	CMT/ACL	9/28/83
Reviewed: D. Green, ACL Manager	CMT/ACL	9/30/83

Distribution of Document C-0030-0303 - Current Standard Operating Procedures
for the Determination of Total Metals in Water by Inductively Coupled
Plasma-Atomic Emission Spectrometry (ICP-AES)

J. Geller

M. Agresta

E. Huff

K. Jensen

D. Green

R. Heinrich

J. Stetter

R. Bane

Original to R. Malecha.

*Document No.
C-0030-0303

Title	Current Standing Operating Procedures for the Determination of Total Metals in Water by ICP-AES
-------	---

Page 1 of 5

This document is fully representative of the Document No. only when the revision number on its pages correspond with those in the index below.

INDEX OF PAGE REVISIONS

[illegible][illegible][illegible][illegible][illegible][illegible]

REVISION AUTHORIZATION

REVISION NUMBER	00	01	02	03	04	05	06	07	08
DCN NUMBER	-								
DATE									
APPROVED BY						.			

1. Scope and Application

- 1.1 This method is applicable to the analysis of aqueous samples from surface, industrial, and municipal origin for the following metals: aluminum, barium, beryllium, boron, cadmium, calcium, chromium, cobalt, copper, iron, lead, magnesium, manganese, molybdenum, nickel, potassium, silver, sodium, strontium, tin, titanium, vanadium, zinc, and zirconium. Potassium and sodium are determined on the sequential system; the remaining elements are part of the polychromator array. The method meets the requirements for National Pollutant Discharge Elimination System (NPDES) monitoring applications.

2. Summary of Method

Samples are digested with nitric acid in accordance with the procedure given in "Methods for Chemical Analysis of Water and Wastes," EMSL, ORD, USEPA, March 1979 (EPA-600 4-79-020). Digests are analyzed by Inductively Coupled Plasma-Atomic Emission Spectrometry (ICP-AES) and results are reported in appropriate concentration units. Twenty-four elements are routinely determined. Additional metals can be obtained from channels on the polychromator or the sequential scanning system.

3. Apparatus

- 3.1 Instruments SA, Inc. ICP-AES system consisting of the following components:

- 3.1.1 A 1-m Paschen-Runge polychromator with a 2550 groves/mm holographic grating.

- 3.1.1.1 Photomultiplier tubes (28).

- 3.1.1.2 Electronics rack (integrators, power supplies).

- 3.1.1.3 Displaceable entrance slit for profiling.

- 3.1.1.4 Entrance and exit slits.

- 3.1.1.5 Mirrors.

- 3.1.1.6 Inert gas purging.

- 3.1.1.7 Temperature control.

- 3.1.2 A 0.64-m Czerny-Turner scanning monochromator with a 1800 groves/mm holographic grating.

- 3.1.2.1 R-955 photomultiplier tube.

- 3.1.2.2 Stepping motor drive and controller.

- 3.1.2.3 Readout electronics.

- 3.1.2.4 Entrance and exit slit.

- 3.1.2.5 Mirrors.

- 3.1.2.6 Inert gas purging.

- 3.1.3 RF Generator, Model HFP-2500, Plasma-Therm with automatic power control and impedance matching network.

- 3.1.3.1 Spray chamber.

3.1.3.2 Quartz torch.

3.1.3.3 Meinhardt concentric nebulizer.

3.2 Computer and Peripherals.

3.2.1 DEC PDP-11/23 with 256K of memory.

3.2.2 DEC RL-02 disc drives (2).

3.2.3 DEC Writer III terminal.

3.2.4 DEC VT-100 terminal with graphics.

3.3 Argon supply (GP45 Liquid).

3.4 Standard glassware and accessories.

4. Reagents

4.1 Acids.

4.1.1 Nitric Acid – Reagent A.C.S. Grade.

4.1.2 Hydrochloric Acid – 6N, Reagent A.C.S. Grade.

4.2 Water. Laboratory distilled water is passed through a SYBRON/Barnstead purification system before use.

4.3 Calibration standards.

4.3.1 Procured from SPEX Industries as certified solutions. Both individual elements or compatible element mixtures are obtained.

4.3.2 Prepared from spectrographically analyzed metals or salts by mineral acid dissolutions.

5. Instrument Operation and Calibration

Details of instrument operation, optimization, and calibration procedures are contained in the manufacturer's instruction handbook and analytical software documentations. These are followed and only the salient features will be discussed.

5.1 Polychromator

5.1.1 The instrument is adjusted for maximum signal to noise ratio by horizontal and vertical translation of the optical window.

5.1.2 Optical alignment is verified by manual profiling of the slit while a standard is being aspirated.

5.1.3 A warm-up period of approximately 30 minutes is allowed before measurements are taken. A satisfactory operating condition prevails, if triplicate exposures on a blank solution show a relative standard deviation of less than 1 percent for each channel.

5.1.4 A two point calibration with blank subtraction is generally used. Four sets of standards (Appendix C) cover the 24 elements generally determined.

5.2 Computer Controlled Scanning Monochromator

- 5.2.1 The instrument is initialized on argon or carbon lines that are always present in an operating argon plasma. These reference wavelengths are typically 588.263 nm for the determination of sodium and 772.421 nm for the potassium measurements.
- 5.2.2 Wavelength calibration is established by analyzing a standard in the peak finding mode.
- 5.2.3 A two point calibration is used. Triplicate measurements are made.

6. Sample Analysis

- 6.1 Sample digests are generally not filtered but are allowed to settle prior to analysis. The instrument calibration is verified by the analysis of a laboratory quality control standard (1000 µg/L). A $\pm 10\%$ deviation is considered a satisfactory calibration. Samples are then analyzed using three 10-second integrations on the polychromator and three 1-second integrations on the monochromator. Approximately every 10th sample, the laboratory quality control standard is re-analyzed to insure the validity of the original instrument calibration. Samples that exceed the high calibration standard are diluted and re-analyzed.

Although the software and hardware configurations allow for on-line background and spectral interference corrections, this approach is currently not practical since the required alternate channels for the determination of high concentration of interfering elements are not in place. As a consequence, an alternate approach is used. Data are generated and filed relating interfering element relationships. Samples for which interference errors are expected to be significant are re-analyzed in the profile mode and appropriate corrections are made manually.

7. Quality Control

Two types of quality control samples are used during an analytical run.

- 7.1 A laboratory quality control standard is analyzed prior to and during an analysis to insure that

- (a) The instrument is properly calibrated.
- (b) Instrument drift is within acceptance levels.
- (c) Sample uptake and nebulization components are functioning satisfactorily.

- 7.2 Sample preparation quality controls are comprised of blanks, spikes, and duplicates. One of each of these is analyzed at an approximate frequency of one per ten samples. Acceptance criteria are consistent with those required by CRL, Region V, USEPA as stated in their "Standard Operating Procedure: Jarrell Ash 1160 Total Metals in Water, March, 1982, Table III."

8. Sample Custody Procedures

Samples received by the ACL are assigned an ACL job number. In addition, the spectrochemical laboratory enters and assigns their own internal identification log number prior to sample processing.

Samples are kept in a locked storage area when not in use.

9. Data Reporting

Data generated by the computer systems are checked for consistency and reported to the originator on a "Spectrochemical Analysis Report" form. This report identifies concentration units, estimated accuracy, and sample identification. Results are reported uncorrected for field blanks.

In addition, quality control information (blanks, duplicates, spikes) are provided with each sample set.

APPENDIX A

POLYCHROMATOR ELEMENTS AND WAVELENGTHS (Å)

CH#	Symbol	Wavelength	Order	CH#?
1	SN	1899.26	1	CH?
2	AR	3393.75	1	CH?
3	MO	2020.30	1	CH?
4	B	2089.59	1	CH?
5	ZN	2138.56	1	CH?
6	FB	2203.53	1	CH?
7	CD	2265.02	1	CH?
8	CO	2286.16	1	CH?
9	NI	2316.04	1	CH?
10	BA	2335.27	1	CH?
11	FE	2382.04	1	CH?
12	RU	2402.72	1	CH?
13	SI	2516.11	1	CH?
14	MN	2576.10	1	CH?
15	CR	2677.16	1	CH?
16	MG	2795.53	1	CH?
17	V	2924.02	1	CH?
18	AL	3082.15	1	CH?
19	BE	3130.42	1	CH?
20	CA	3158.87	1	CH?
21	CU	3247.54	1	CH?
22	AG	3280.68	1	CH?
23	TI	3349.41	1	CH?
24	TL	1908.01	1	CH?
25	ZR	3438.23	1	CH?
26	NI	4061.09	1	CH?
27	SR	4077.71	1	CH?
28	CE	4137.65	1	CH?
29	640	0.00	1	CH?

APPENDIX B

DETECTION LIMITS ($\mu\text{g/L}$)

08-SEP-83 10:12:10

Symbol	D.L.(3X)	Conc.	Net int.	Blk.int.	%S.D.
SN	80.29	4000.	5901.	832.4	4.743
TL	49.95	4000.	1.2509E+04	1461.	3.564
ZN	1.210	4000.	9.8824E+04	1476.	0.6752
PB	20.52	4000.	7935.	1868.	0.7265
CD	1.907	4000.	8.3713E+04	1917.	0.6940
CO	2.892	4000.	3.8874E+04	1216.	0.7704
NI	6.771	4000.	2.0667E+04	1443.	0.8081
BA	1.448	4000.	9.1002E+04	1658.	0.6625
FE	2.472	4000.	2.3538E+04	751.8	0.6450
MN	0.3975	4000.	2.2253E+05	1171.	0.6295
CR	2.580	4000.	3.1801E+04	1049.	0.6519
MG	0.4441	4000.	1.0691E+05	488.9	0.8093
V	1.417	4000.	5.1471E+04	1579.	0.3848
AL	9.461	4000.	2.0886E+04	3994.	0.4123
BE	0.1719	4000.	3.1972E+05	677.1	0.6766
CA	7.253	4000.	1.4782E+04	2348.	0.3805
CU	1.403	4000.	6.1425E+04	1395.	0.5148
ZR	0.9830	4000.	1.0603E+05	2375.	0.3657
SR	0.2162	4000.	1.9013E+05	469.8	0.7291

Output another terminal?

08-SEP-83 10:13:18

Symbol	D.L.(3X)	Conc.	Net int.	Blk.int.	%S.D.
MO	7.240	5000.	5.2631E+04	1679.	1.513
B	8.171	5000.	6.2263E+04	1787.	1.898
SI	445.5	5000.	5045.	3774.	3.970
TI	1.191	5000.	7.9483E+04	977.4	0.6456

Output another terminal?

08-SEP-83 10:14:29

Symbol	D.L.(3X)	Conc.	Net int.	Blk.int.	%S.D.
AG	2.201	4000.	2.9134E+04	1126.	0.4745

Output another terminal?

APPENDIX C

CALIBRATION STANDARDS
(Ca, Mg: $\mu\text{g/mL}$; all others: $\mu\text{g/L}$)

NO.	CH#	Symbol	LoStd	Concentration	HiStd	Concentration	NO.?
1	2	AR	0	0.00000	0	0.00000	CH?
2	20	CA	1	0.00000	4	50.00000	CH?
3	16	MG	1	0.00000	4	10.00000	CH?
4	18	AL	1	0.00000	2	4000.00000	CH?
5	10	BA	1	0.00000	2	4000.00000	CH?
6	19	BE	1	0.00000	2	4000.00000	CH?
7	7	CD	1	0.00000	2	4000.00000	CH?
8	8	CO	1	0.00000	2	4000.00000	CH?
9	15	CR	1	0.00000	2	4000.00000	CH?
10	21	CU	1	0.00000	2	4000.00000	CH?
11	11	FE	1	0.00000	2	4000.00000	CH?
12	14	MN	1	0.00000	2	4000.00000	CH?
13	9	NI	1	0.00000	2	4000.00000	CH?
14	6	PB	1	0.00000	2	4000.00000	CH?
15	1	SN	1	0.00000	2	4000.00000	CH?
16	27	SR	1	0.00000	2	4000.00000	CH?
17	24	TL	1	0.00000	2	4000.00000	CH?
18	17	V	1	0.00000	2	4000.00000	CH?
19	5	ZN	1	0.00000	2	4000.00000	CH?
20	25	ZR	1	0.00000	2	4000.00000	CH?
21	4	B	1	0.00000	3	5000.00000	CH?
22	3	MO	1	0.00000	3	5000.00000	CH?
23	23	TI	1	0.00000	3	5000.00000	CH?
24	22	AG	1	0.00000	5	4000.00000	CH?

APPENDIX D

ANALYTICAL CONDITIONS FOR SODIUM ANALYSIS

Y

SYMBOL WAVELENGTH BKGD CORR OFFSET
 NA 589.0000 LOW= 0.0000 HIGH= 0.0000
 INTEGRATION TIME # MEASUREMENTS RECAL STANDARDS
 500 MSEC 1 LOW= 1 HIGH= 5
 CONC=-0.2989803 + 2.0661726E-04*I + 0.0000000 I² WEIGHTED= F

STD #	CONC	STD #	CONC	STD #	CONC
1	0.0000	6	-1.000	11	-1.000
2	10.00	7	-1.000	12	-1.000
3	20.00	8	-1.000	13	-1.000
4	50.00	9	-1.000	14	-1.000
5	100.0	10	-1.000	15	-1.000

 DETECTION LIMIT= 2.9000E-02 PPM

SYMBOL WAVELENGTH BKGD CORR OFFSET
 NA 589.6020 LOW= 0.0000 HIGH= 0.0000
 INTEGRATION TIME # MEASUREMENTS RECAL STANDARDS
 500 MSEC 1 LOW= 1 HIGH= 5
 CONC=-0.3949023 + 4.3561839E-04*I + 0.0000000 I² WEIGHTED= F

STD #	CONC	STD #	CONC	STD #	CONC
1	0.0000	6	-1.000	11	-1.000
2	10.00	7	-1.000	12	-1.000
3	20.00	8	-1.000	13	-1.000
4	50.00	9	-1.000	14	-1.000
5	100.0	10	-1.000	15	-1.000

 DETECTION LIMIT= 6.9000E-02 PPM

588.263 SEQUENTIAL: ANALYSIS CALIBRATE FILER TABLE??

APPENDIX E

ANALYTICAL CONDITIONS FOR POTASSIUM ANALYSIS

Y

SYMBOL WAVELENGTH BKGD CORR OFFSET
K 766.5260 LOW= 0.0000 HIGH= 0.0000

INTEGRATION TIME # MEASUREMENTS RECAL STANDARDS
500 MSEC 1 LOW= 1 HIGH= 4

CONC= -1.317425 + 1.3457629E-03*I + 0.0000000 I² WEIGHTED= F

STD #	CONC	STD #	CONC	STD #	CONC
1	0.0000	6	-1.000	11	-1.000
2	10.00	7	-1.000	12	-1.000
3	20.00	8	-1.000	13	-1.000
4	50.00	9	-1.000	14	-1.000
5	100.0	10	-1.000	15	-1.000

DETECTION LIMIT= 0.1000 PPM

SYMBOL WAVELENGTH BKGD CORR OFFSET
K 769.9340 LOW=-0.0500 HIGH= 0.0500

INTEGRATION TIME # MEASUREMENTS RECAL STANDARDS
500 MSEC 1 LOW= 1 HIGH= 4

CONC=-8.3477467E-02+ 2.9510655E-03*I + 0.0000000 I² WEIGHTED= F

STD #	CONC	STD #	CONC	STD #	CONC
1	0.0000	6	-1.000	11	-1.000
2	10.00	7	-1.000	12	-1.000
3	20.00	8	-1.000	13	-1.000
4	50.00	9	-1.000	14	-1.000
5	100.0	10	-1.000	15	-1.000

DETECTION LIMIT= 0.1000 PPM

588.263 SEQUENTIAL: ANALYSIS CALIBRATE FILER TABLE??

Documentation for Briquette Surface Chemistry Files
 Anion files (sulfate, nitrate, chlorine, fluorine)
 Separate files for limestone and marble

COLUMN HEADINGS:

SITE = Field Site; MAT = Material Type; PER = Exposure Period;
 SYR = Start Year (of exposure); SJD = Start Julian Date; EYR = End Year; EJD = End Julian Date;
 SLOT = Briquette Slot Location; SAMPLE = Briquette Sample Number; LAY = Layer Designation;
 SO4=sulfate; NO3=nitrate; CL=chlorine; FL=fluorine

Flags ("<") for results below detection limit are found in adjacent column to the right:

DS=Detection Limit for Sulfate DN=Detection Limit for Nitrate
 DC=Detection Limit for Chlorine DF=Detection Limit for Fluorine

KEY TO SPECIFIC ENTRIES:

SITES -----

CB=Characterization
 NC=North Carolina
 NJ=New Jersey
 NY=New York
 DC=Washington DC
 OH=Ohio
 OHM=Ohio Moveable Shelter
 (Sprayed and Dry regimes)

MATERIAL TYPES -----

FL=Fresh Limestone WL=Weathered Limestone
 FM=Fresh Marble WM=Weathered Marble
 SFL=Sprayed regime FL SWL=Sprayed regime WL
 SFM=Sprayed regime FM SWM=Sprayed regime WM
 DFL=Dry Regime FL DWL=Dry regime WL
 DFM=Dry regime FM DWM=Dry regime WM

TIME PERIODS -----

Quarters = 1, 2, 3, 4, 5, etc.
 Annuals = A1, A2, A3, etc. (Ax, where x is 1-5th year)
 Biennials = B1, B2, etc. (Bx, where x is 1-3rd biennial cycle)
 Triennial = T1, T2 (1st and 2nd triennial cycles)
 Quadrennial = Q1 (1st quadrennial cycle)
 Quinquennial = C1

LAYERS-----

A,B,C=Top 3 layers
 (A=outermost top layer)
 U,V,W,X,Y,Z=Bottom layers
 (Z=outermost bottom layer)

COMMENTS-----

AGG=Analysis of aggregated sample
 BULK=Analysis of volumetric center of briquette
 ICP=Sample also analyzed for cations (see cation files) NA, N1, N2, and N3 = not applicable
 ICP*=Sample analyzed for cations was an aggregated sample

MISC.-----

< = flag for result below detection limit
 ? = analytical result questioned by chem lab

PRE-EXPOSED LIMESTONE BASELINE (1988)

SITE	MAT	PER	SYR	SJD	EYR	EJD	SLOT	SAMPLE	LAY	SO4	DS	NO3	DN	CL	DC	FL	DF	COMMENTS
=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	1	19600		40		36		79		A:0-10ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	3	28800		45		38		48		C:20-30ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	6	10600		32		34		32		F:50-60ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	8	3080		26		33		22		90-100ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	10	2270		40		35		10	<	240-260ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	12	1290		22		34		10	<	480-500ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	14	1180		21		30		10	<	720-760ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	16	250		20		36		10	<	1480-1520ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-06	20	279		17		31		10	<	1990-2000ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	1	6600		17	<	24		50		A:0-10ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	3	2230		18		32		47		C:20-30ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	6	23400		20		33		39		F:50-60ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	8	5650		17	<	30		34		90-100ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	10	2620		17		31		17		240-260ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	12	2485		21		39		10	<	480-500ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	14	1030		23		35		10	<	720-760ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	16	149		17	<	27		10	<	1480-1520ml
C8	WL	NA	NA	NA	NA	NA	NA	PW1-05	20	172	~	17	<	28		10	<	1990-2000ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	1	22700		57		46		68		A:0-10ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	3	19800		54		54		46		C:20-30ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	6	10100		37		42		32		F:50-60ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	8	3930		28		36		24		90-100ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	10	2460		48		36		11		240-260ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	12	1460		24		29		10	<	480-500ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	14	817		20		28		10	<	720-760ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	16	146		17	<	21		10	<	1480-1520ml
C8	WL	NA	NA	NA	NA	NA	NA	YW1-16	20	246		47		31		10	<	1990-2000ml

PRE-EXPOSED MARBLE BASELINE / 1988

SITE	MAT	PER	SYR	SJD	EYR	EJD	SLOT	SAMPLE	LAY	SO4	DS	NO3	DN	CL	DC	FL	DF	COMMENTS
CB	WM	NA	NA	NA	NA	NA	NA	W23-32	1	136		41		103		5		< A: 0-10ml
CB	WM	NA	NA	NA	NA	NA	NA	W23-32	3	196		29		57		5		< B: 20-30ml
CB	WM	NA	NA	NA	NA	NA	NA	W23-32	6	200		29		58		5		< C: 50-60ml
CB	WM	NA	NA	NA	NA	NA	NA	W22-31	1	1800		20		27		6		A: 0-10ml
CB	WM	NA	NA	NA	NA	NA	NA	W22-31	3	148		18		25		5		< B: 20-30ml
CB	WM	NA	NA	NA	NA	NA	NA	W22-31	6	104		19		32		5		< C: 50-60ml
CB	WM	NA	NA	NA	NA	NA	NA	AC-1	1	33		13		16		5		< A: 0-10ml
CB	WM	NA	NA	NA	NA	NA	NA	AC-1	3	20		10		12		5		< B: 20-30ml
CB	WM	NA	NA	NA	NA	NA	NA	AC-1	6	45		10		13		5		< C: 50-60ml

LIMESTONE ANION CONCENTRATIONS / 1984-1988

SITE	MAT	PER	SYR	SJD	EYR	EJD	SLOT	SAMPLE	LAY	SO4	DS	NO3	DN	CL	DC	FL	DF	COMMENTS
====	====	====	====	====	====	====	====	=====	====	=====	==	=====	==	====	====	====	====	=====
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	NA	88		15 <		35		4		BULK
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	NA	65		15 <		24		5		BULK
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	NA	72		15 <		26		5		BULK
CB	FL	NA	NA	NA	NA	NA	N1	GU7-07	A	400		15 <		150		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	GU7-07	B	120		15 <		90		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	GU7-07	C	105		15 <		75		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	A	170		15 <		30		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	B	90		15 <		30		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	C	85		15 <		30		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	X	68		15 <		23		5		
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	Y	68		15 <		24		5		
CB	FL	NA	NA	NA	NA	NA	N1	HU4-22	Z	80		15 <		28		4		
CB	FL	NA	NA	NA	NA	NA	N1	IU2-17	A	150		15 <		55		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	IU2-17	B	75		15 <		40		10 <		ICP
CB	FL	NA	NA	NA	NA	NA	N1	IU2-17	C	70		15 <		35		10 <		ICP
NC	FL	1	84	146	84	237	131	HU4-06	A	65		15 <		15		10 <		ICP
NC	FL	1	84	146	84	237	131	HU4-06	B	65		15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	131	HU4-06	C	60	-	15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	131	HU4-06	Z	2089		50		45		6		
NC	FL	1	84	146	84	237	144	GU1-18	A	85		15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	144	GU1-18	B	90		15 <		25		10 <		ICP
NC	FL	1	84	146	84	237	144	GU1-18	C	80		15 <		30		10 <		ICP
NC	FL	1	84	146	84	237	150	IU2-01	A	90		15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	150	IU2-01	B	75		15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	150	IU2-01	C	70		15 <		20		10 <		ICP
NC	FL	1	84	146	84	237	150	IU2-01	X	135		15		34		6		
NC	FL	1	84	146	84	237	150	IU2-01	Y	178		14		34		6		
NC	FL	1	84	146	84	237	150	IU2-01	Z	2120		29		34		7		
NC	FL	2	84	237	84	331	131	HL5-23	A	126		15 <		19		5		
NC	FL	2	84	237	84	331	131	HL5-23	B	92		15 <		23		5 <		
NC	FL	2	84	237	84	331	131	HL5-23	C	91		15 <		24		5 <		
NC	FL	2	84	237	84	331	144	HU5-19	A	101		15 <		15		7		
NC	FL	2	84	237	84	331	144	HU5-19	B	79		15 <		16		7		
NC	FL	2	84	237	84	331	144	HU5-19	C	75		15 <		16		7		
NC	FL	2	84	237	84	331	150	HU5-01	A	117		15 <		19		5 <		
NC	FL	2	84	237	84	331	150	HU5-01	B	98		15 <		22		5 <		
NC	FL	2	84	237	84	331	150	HU5-01	C	86		15 <		25		5 <		
NC	FL	2	84	237	84	331	150	HU5-01	X	132		56		64		10		
NC	FL	2	84	237	84	331	150	HU5-01	Y	247		53		60		9		
NC	FL	2	84	237	84	331	150	HU5-01	Z	2908		73		68		11		
NC	FL	3	84	331	85	60	131	GU4-06	A	91		10 <		16		4		
NC	FL	3	84	331	85	60	131	GU4-06	B	85		10 <		19		4		
NC	FL	3	84	331	85	60	131	GU4-06	C	82		10 <		21		4		
NC	FL	3	84	331	85	60	144	HL6-06	A	92		10 <		18		4		
NC	FL	3	84	331	85	60	144	HL6-06	B	86		10 <		19		4		

NC	FL	3	84	331	85	60	144	HL6-06	C	81	10 <	19	4	
NC	FL	3	84	331	85	60	144	HL6-06	X	200	16	28	6	
NC	FL	3	84	331	85	60	144	HL6-06	Y	208	13	27	6	
NC	FL	3	84	331	85	60	144	HL6-06	Z	2550	14	26	6	
NC	FL	3	84	331	85	60	150	GU4-20	A	96	10 <	16	4	
NC	FL	3	84	331	85	60	150	GU4-20	B	89	10 <	18	4	
NC	FL	3	84	331	85	60	150	GU4-20	C	84	10 <	18	4	
NC	FL	4	85	60	85	136	131	HL6-23	A	71	27	44	5	
NC	FL	4	85	60	85	136	131	HL6-23	B	61	17	28	5	
NC	FL	4	85	60	85	136	131	HL6-23	C	61	14	27	4	
NC	FL	4	85	60	85	136	144	GU4-14	A	64	10 <	25	4	
NC	FL	4	85	60	85	136	144	GU4-14	B	71	12	28	4	
NC	FL	4	85	60	85	136	144	GU4-14	C	71	12	28	4	
NC	FL	4	85	60	85	136	144	GU4-14	X	118	10 <	27	5	
NC	FL	4	85	60	85	136	144	GU4-14	Y	115	10	26	5	
NC	FL	4	85	60	85	136	144	GU4-14	Z	121	10	23	5	
NC	FL	4	85	60	85	136	150	HL6-02	A	58	25	27	6	
NC	FL	4	85	60	85	136	150	HL6-02	B	66	50	30	6	
NC	FL	4	85	60	85	136	150	HL6-02	C	64	18	28	5	
NC	FL	5	85	136	85	240	N1	NA	A	65	15 <	20	5	AGG
NC	FL	5	85	136	85	240	N1	NA	B	65	15 <	20	10	AGG
NC	FL	5	85	136	85	240	N1	NA	Y	185	35	25	10	AGG
NC	FL	5	85	136	85	240	N1	NA	Z	1245	15 <	25	10	AGG
NC	FL	6	85	240	85	331	N1	NA	A	65	15 <	15	5	AGG
NC	FL	6	85	240	85	331	N1	NA	B	70	15 <	20	5	AGG
NC	FL	6	85	240	85	331	N1	NA	Y	120	15 <	20	10	AGG
NC	FL	6	85	240	85	331	N1	NA	Z	520	20	20	10	AGG
NC	FL	7	85	331	86	62	N1	NA	A	130	15 <	15	10	AGG
NC	FL	7	85	331	86	62	N1	NA	B	100	15 <	20	10	AGG
NC	FL	7	85	331	86	62	N1	NA	Y	295	335	30	10	AGG
NC	FL	7	85	331	86	62	N1	NA	Z	270	15 <	25	10	AGG
NC	FL	8	86	62	86	155	N1	NA	A	90	20	20	7	AGG
NC	FL	8	86	62	86	155	N1	NA	B	70	15 <	20	5	AGG
NC	FL	8	86	62	86	155	N1	NA	Y	680	110	90	10	AGG
NC	FL	8	86	62	86	155	N1	NA	Z	3635	105	105	10	AGG
NC	FL	A1	84	146	85	136	103	HL5-04	A	54	8	20	4	ICP
NC	FL	A1	84	146	85	136	103	HL5-04	B	64	8	21	7	ICP
NC	FL	A1	84	146	85	136	103	HL5-04	C	59	13	22	8	ICP
NC	FL	A1	84	146	85	136	103	HL5-04	X	225	21	24	11	ICP
NC	FL	A1	84	146	85	136	103	HL5-04	Y	260	22	25	11	ICP
NC	FL	A1	84	146	85	136	103	HL5-04	Z	5461	31	22	8	ICP
NC	FL	A1	84	146	85	136	127	IL5-20	A	56	8 <	16	5	ICP
NC	FL	A1	84	146	85	136	127	IL5-20	B	66	8 <	17	5	ICP
NC	FL	A1	84	146	85	136	127	IL5-20	C	82	11	17	6	ICP
NC	FL	A1	84	146	85	136	127	IL5-20	Z	6932	104	40	9	
NC	FL	A1	84	146	85	136	136	GL5-07	A	54	8	18	8	ICP
NC	FL	A1	84	146	85	136	136	GL5-07	B	58	12	21	9	ICP
NC	FL	A1	84	146	85	136	136	GL5-07	C	60	8 <	20	6	ICP
NC	FL	A2	85	136	86	155	N1	NA	A	90	20	25	5	AGG

NC	FL	A2	85	136	86	155	N2	NA	B	60	15	25	5	AGG
NC	FL	A2	85	136	86	155	N3	NA	C	70	15 <	25	5	AGG
NC	FL	A2	85	136	86	155	136	HL6-05	X	360	240	60	10	
NC	FL	A2	85	136	86	155	136	HL6-05	Y	405	240	60	10	
NC	FL	A2	85	136	86	155	136	HL6-05	Z	9550	290	65	15	
NC	FL	A4	87	160	88	188	103	HL8-14	A	840	36	17	9	
NC	FL	A4	87	160	88	188	103	HL8-14	U	67	17 <	15	8 <	
NC	FL	A4	87	160	88	188	103	HL8-14	V	82	29	17	8 <	
NC	FL	A4	87	160	88	188	103	HL8-14	W	79	17 <	16	8 <	
NC	FL	A4	87	160	88	188	103	HL8-14	X	82	17 <	17	8 <	
NC	FL	A4	87	160	88	188	103	HL8-14	Y	80	17 <	17	8 <	
NC	FL	A4	87	160	88	188	103	HL8-14	Z	80	17 <	14	8 <	
NC	FL	A4	87	160	88	188	127	IL8-10	A	59	17 <	14	15	
NC	FL	A4	87	160	88	188	127	IL8-10	X	203	144	38	19	
NC	FL	A4	87	160	88	188	127	IL8-10	Y	600	125	37	19	
NC	FL	A4	87	160	88	188	127	IL8-10	Z	12500	195	41	20	
NC	FL	A4	87	160	88	188	136	GL6-13	A	60	17 <	16	15	
NC	FL	A4	87	160	88	188	136	GL6-13	U	110	162	43	17	
NC	FL	A4	87	160	88	188	136	GL6-13	V	112	148	40	17	
NC	FL	A4	87	160	88	188	136	GL6-13	W	127	144	40	18	
NC	FL	A4	87	160	88	188	136	GL6-13	X	135	138	38	18	
NC	FL	A4	87	160	88	188	136	GL6-13	Y	314	110	41	19	
NC	FL	A4	87	160	88	188	136	GL6-13	Z	9000	130	40	21	
NC	FL	B1	84	146	86	155	102	IU5-05	A	95	15 <	20	5	ICP
NC	FL	B1	84	146	86	155	102	IU5-05	B	70	15 <	20	5	ICP*
NC	FL	B1	84	146	86	155	102	IU5-05	C	75	15 <	20	5	ICP*
NC	FL	B1	84	146	86	155	102	IU5-05	Z	12800	28	57	13	
NC	FL	B1	84	146	86	155	139	HL4-17	A	100	20	20	5	ICP
NC	FL	B1	84	146	86	155	139	HL4-17	B	105	15 <	25	5	ICP*
NC	FL	B1	84	146	86	155	139	HL4-17	C	80	15 <	25	5	ICP*
NC	FL	B1	84	146	86	155	139	HL4-17	X	330	200	45	10	ICP
NC	FL	B1	84	146	86	155	139	HL4-17	Y	505	205	45	10	ICP
NC	FL	B1	84	146	86	155	139	HL4-17	Z	9675	325	55	20	ICP
NC	FL	B1	84	146	86	155	159	GL2-10	A	105	20	20	5	ICP
NC	FL	B1	84	146	86	155	159	GL2-10	B	80	15 <	25	5	ICP*
NC	FL	B1	84	146	86	155	159	GL2-10	C	85	15 <	20	5	ICP*
NC	FL	T1	84	146	87	160	128	HU4-02	A	116	9	15	6	
NC	FL	T1	84	146	87	160	128	HU4-02	X	780	100	41	10	
NC	FL	T1	84	146	87	160	128	HU4-02	Y	3715	106	47	13	
NC	FL	T1	84	146	87	160	128	HU4-02	Z	25000	165	43	38	
NC	FL	T1	84	146	87	160	138	GU7-14	A	108	13	19	6	
NC	FL	T1	84	146	87	160	138	GU7-14	X	540	79	49	18	
NC	FL	T1	84	146	87	160	138	GU7-14	Y	925	78	48	16	
NC	FL	T1	84	146	87	160	138	GU7-14	Z	20500	125	63	34	
NC	FL	T1	84	146	87	160	148	IU2-22	A	112	9	16	6	
NC	FL	T1	84	146	87	160	148	IU2-22	X	475	93	50	18	
NC	FL	T1	84	146	87	160	148	IU2-22	Y	1100	91	66	28	
NC	FL	T1	84	146	87	160	148	IU2-22	Z	20500	150	45	32	
NC	FL	Q1	84	146	88	188	124	HU5-16	A	55	34	19	16	

NC	FL	Q1	84	146	88	188	124	HU5-16	U	252	82	28	20	
NC	FL	Q1	84	146	88	188	124	HU5-16	V	216	75	28	19	
NC	FL	Q1	84	146	88	188	124	HU5-16	W	303	90	28	20	
NC	FL	Q1	84	146	88	188	124	HU5-16	X	396	65	21	21	
NC	FL	Q1	84	146	88	188	124	HU5-16	Y	920	67	22	23	
NC	FL	Q1	84	146	88	188	124	HU5-16	Z	20500	114	25	43	
NC	FL	Q1	84	146	88	188	105	IL4-14	A	55	36	21	16	
NC	FL	Q1	84	146	88	188	105	IL4-14	U	110	92	30	19	
NC	FL	Q1	84	146	88	188	105	IL4-14	V	123	97	25	20	
NC	FL	Q1	84	146	88	188	105	IL4-14	W	127	72	28	20	
NC	FL	Q1	84	146	88	188	105	IL4-14	X	221	61	24	21	
NC	FL	Q1	84	146	88	188	105	IL4-14	Y	1400	58	26	25	
NC	FL	Q1	84	146	88	188	105	IL4-14	Z	18000	104	20	45	
NC	FL	Q1	84	146	88	188	108	GL2-21	A	56	17 <	20	8	
NC	FL	Q1	84	146	88	188	108	GL2-21	X	188	70	28	12	
NC	FL	Q1	84	146	88	188	108	GL2-21	Y	1050	66	32	14	
NC	FL	Q1	84	146	88	188	108	GL2-21	Z	19800	103	25	28	
NJ	FL	1	84	157	84	251	131	HU4-10	A	100	15 <	20	10 <	ICP
NJ	FL	1	84	157	84	251	131	HU4-10	B	80	15 <	20	10 <	ICP
NJ	FL	1	84	157	84	251	131	HU4-10	C	60	15 <	15	10 <	ICP
NJ	FL	1	84	157	84	251	144	GU1-15	A	90	15 <	30	10 <	ICP
NJ	FL	1	84	157	84	251	144	GU1-15	B	85	15 <	30	10 <	ICP
NJ	FL	1	84	157	84	251	144	GU1-15	C	70	15 <	20	10 <	ICP
NJ	FL	1	84	157	84	251	150	IU2-05	A	100	15 <	20	10 <	ICP
NJ	FL	1	84	157	84	251	150	IU2-05	B	90	15 <	25	10 <	ICP
NJ	FL	1	84	157	84	251	150	IU2-05	C	85	15 <	20	10 <	ICP
NJ	FL	1	84	157	84	251	150	IU2-05	X	188	41	31	6	
NJ	FL	1	84	157	84	251	150	IU2-05	Y	189	33	36	6	
NJ	FL	1	84	157	84	251	150	IU2-05	Z	4904	71	34	6	
NJ	FL	2	84	251	84	349	131	HU5-15	A	262	15 <	19	5 <	
NJ	FL	2	84	251	84	349	131	HU5-15	B	124	15 <	23	5 <	
NJ	FL	2	84	251	84	349	131	HU5-15	C	111	15 <	22	5 <	
NJ	FL	2	84	251	84	349	144	IU4-10	A	206	15 <	16	7	
NJ	FL	2	84	251	84	349	144	IU4-10	B	124	15 <	17	7	
NJ	FL	2	84	251	84	349	144	IU4-10	C	105	15 <	17	7	
NJ	FL	2	84	251	84	349	150	IU4-14	A	208	15 <	19	8	
NJ	FL	2	84	251	84	349	150	IU4-14	B	120	15 <	18	7	
NJ	FL	2	84	251	84	349	150	IU4-14	C	98	15 <	17	7	
NJ	FL	2	84	251	84	349	150	IU4-14	X	145	22	30	11	
NJ	FL	2	84	251	84	349	150	IU4-14	Y	170	27	29	10	
NJ	FL	2	84	251	84	349	150	IU4-14	Z	3176	38	30	12	
NJ	FL	3	84	349	85	65	131	HL6-09	A	113	10 <	20	4	
NJ	FL	3	84	349	85	65	131	HL6-09	B	105	10 <	22	5	
NJ	FL	3	84	349	85	65	131	HL6-09	C	99	10 <	22	5	
NJ	FL	3	84	349	85	65	144	HL6-19	A	116	10 <	17	4	
NJ	FL	3	84	349	85	65	144	HL6-19	B	107	10 <	19	4	
NJ	FL	3	84	349	85	65	144	HL6-19	C	96	10 <	20	4	
NJ	FL	3	84	349	85	65	144	HL6-19	X	191	20	34	6	

NJ	FL	3	84	349	85	65	144	HL6-19	Y	252	17	32	6	
NJ	FL	3	84	349	85	65	144	HL6-19	Z	4310	25	36	6	
NJ	FL	3	84	349	85	65	150	GU4-23	A	132	10 <	22	4	
NJ	FL	3	84	349	85	65	150	GU4-23	B	98	10 <	23	4	
NJ	FL	3	84	349	85	65	150	GU4-23	C	95	10 <	22	5	
NJ	FL	4	85	65	85	158	131	GU4-24	A	75	10 <	19	3	
NJ	FL	4	85	65	85	158	131	GU4-24	B	75	38	22	4	
NJ	FL	4	85	65	85	158	131	GU4-24	C	71	10 <	22	4	
NJ	FL	4	85	65	85	158	144	HL6-01	A	78	10	19	4	
NJ	FL	4	85	65	85	158	144	HL6-01	B	84	10 <	22	4	
NJ	FL	4	85	65	85	158	144	HL6-01	C	77	10 <	21	4	
NJ	FL	4	85	65	85	158	144	HL6-01	X	264	36	33	6	
NJ	FL	4	85	65	85	158	144	HL6-01	Y	252	36	32	6	
NJ	FL	4	85	65	85	158	144	HL6-01	Z	5190	47	33	5	
NJ	FL	4	85	65	85	158	150	GU4-18	A	76	10 <	21	4	
NJ	FL	4	85	65	85	158	150	GU4-18	B	80	10 <	24	4	
NJ	FL	4	85	65	85	158	150	GU4-18	C	79	10 <	23	4	
NJ	FL	A1	84	157	85	158	103	HL5-13	A	85	9 <	20	4	
NJ	FL	A1	84	157	85	158	103	HL5-13	B	82	9 <	21	4	
NJ	FL	A1	84	157	85	158	103	HL5-13	C	78	9 <	20	4	
NJ	FL	A1	84	157	85	158	127	IL5-17	A	71	9 <	19	4	
NJ	FL	A1	84	157	85	158	127	IL5-17	B	78	9 <	21	4	
NJ	FL	A1	84	157	85	158	127	IL5-17	C	76	9 <	22	4	
NJ	FL	A1	84	157	85	158	127	IL5-17	X	440	34	27	6	
NJ	FL	A1	84	157	85	158	127	IL5-17	Y	1150	39	27	7	
NJ	FL	A1	84	157	85	158	127	IL5-17	Z	12570	92	30	6	
NJ	FL	A1	84	157	85	158	136	GL5-04	A	79	9 <	21	4	
NJ	FL	A1	84	157	85	158	136	GL5-04	B	79	9 <	23	4	
NJ	FL	A1	84	157	85	158	136	GL5-04	C	79	9 <	24	4	
NJ	FL	A1	84	157	85	158	136	GL5-04	Z	9714	89	34	9	
NJ	FL	A2	85	158	86	169	N1	NA	A	75	15 <	25	10	AGG
NJ	FL	A2	85	158	86	169	N2	NA	B	75	15 <	25	10	AGG
NJ	FL	A2	85	158	86	169	N3	NA	C	70	15 <	20	10	AGG
NJ	FL	A2	85	158	86	169	127	HL6-13	X	570	15	25	10	
NJ	FL	A2	85	158	86	169	127	HL6-13	Y	500	15	25	10	
NJ	FL	A2	85	158	86	169	127	HL6-13	Z	12900	25	25	10	
NJ	FL	B1	84	157	86	169	102	IU5-07	A	60	15 <	15	5	ICP
NJ	FL	B1	84	157	86	169	102	IU5-07	B	70	15 <	20	5	ICP*
NJ	FL	B1	84	157	86	169	102	IU5-07	C	65	15 <	15	5	ICP*
NJ	FL	B1	84	157	86	169	102	IU5-07	Z	19000	61	26	11	
NJ	FL	B1	84	157	86	169	139	HL4-09	A	60	15 <	15	5	ICP
NJ	FL	B1	84	157	86	169	139	HL4-09	B	70	15 <	15	10	ICP*
NJ	FL	B1	84	157	86	169	139	HL4-09	C	80	15 <	20	10	ICP*
NJ	FL	B1	84	157	86	169	139	HL4-09	X	470	20	25	10	ICP
NJ	FL	B1	84	157	86	169	139	HL4-09	Y	490	20	20	10	ICP
NJ	FL	B1	84	157	86	169	139	HL4-09	Z	9980	40	20	15	ICP
NJ	FL	B1	84	157	86	169	159	GL2-17	A	70	15 <	15	5	ICP
NJ	FL	B1	84	157	86	169	159	GL2-17	B	70	15 <	15	10	ICP*
NJ	FL	B1	84	157	86	169	159	GL2-17	C	65	15 <	20	10	ICP*

NY	FL	1	84	171	84	269	131	HU4-14	A	70	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	131	HU4-14	B	75	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	131	HU4-14	C	80	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	144	GU1-14	A	45	15 <	15	10 <	ICP
NY	FL	1	84	171	84	269	144	GU1-14	B	50	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	144	GU1-14	C	50	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	150	IU2-09	A	65	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	150	IU2-09	B	65	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	150	IU2-09	C	60	15 <	20	10 <	ICP
NY	FL	1	84	171	84	269	150	IU2-09	X	126	12 <	28	6	
NY	FL	1	84	171	84	269	150	IU2-09	Y	134	12 <	27	6	
NY	FL	1	84	171	84	269	150	IU2-09	Z	1499	12 <	26	6	
NY	FL	2	84	269	84	356	131	IU2-13	A	68	15 <	23	5 <	
NY	FL	2	84	269	84	356	131	IU2-13	B	71	15 <	25	5 <	
NY	FL	2	84	269	84	356	131	IU2-13	C	61	15 <	24	5 <	
NY	FL	2	84	269	84	356	150	GU4-21	A	64	15 <	19	5 <	
NY	FL	2	84	269	84	356	150	GU4-21	B	64	15 <	20	5 <	
NY	FL	2	84	269	84	356	150	GU4-21	C	64	15 <	21	5 <	
NY	FL	2	84	269	84	356	144	HU6-13	A	64	15 <	19	5 <	
NY	FL	2	84	269	84	356	144	HU6-13	B	63	15 <	22	5 <	
NY	FL	2	84	269	84	356	144	HU6-13	C	63	15 <	22	5 <	
NY	FL	2	84	269	84	356	144	HU6-13	X	76	15 <	24	9	
NY	FL	2	84	269	84	356	144	HU6-13	Y	85	15 <	25	9	
NY	FL	2	84	269	84	356	144	HU6-13	Z	91	15 <	24	9	
NY	FL	3	84	356	85	79	131	GU4-17	A	72	10 <	16	3	
NY	FL	3	84	356	85	79	131	GU4-17	B	72	10 <	19	4	
NY	FL	3	84	356	85	79	131	GU4-17	C	70	10 <	19	4	
NY	FL	3	84	356	85	79	144	HL6-16	A	68	10 <	15	4	
NY	FL	3	84	356	85	79	144	HL6-16	B	68	10 <	18	4	
NY	FL	3	84	356	85	79	144	HL6-16	C	64	10 <	17	4	
NY	FL	3	84	356	85	79	144	HL6-16	X	186	10 <	26	5	
NY	FL	3	84	356	85	79	144	HL6-16	Y	191	10	20	6	
NY	FL	3	84	356	85	79	144	HL6-16	Z	1040	10	22	5	
NY	FL	3	84	356	85	79	150	HL6-22	A	78	10 <	17	4	
NY	FL	3	84	356	85	79	150	HL6-22	B	74	10 <	17	4	
NY	FL	3	84	356	85	79	150	HL6-22	C	72	10 <	18	5	
NY	FL	4	85	79	85	172	131	GU4-03	A	64	11	22	4	
NY	FL	4	85	79	85	172	131	GU4-03	B	66	10	24	4	
NY	FL	4	85	79	85	172	131	GU4-03	C	68	13	23	4	
NY	FL	4	85	79	85	172	144	HL6-11	A	49	19	27	5	
NY	FL	4	85	79	85	172	144	HL6-11	B	57	11	25	5	
NY	FL	4	85	79	85	172	144	HL6-11	C	58	13	24	4	
NY	FL	4	85	79	85	172	144	HL6-11	X	122	10	28	5	
NY	FL	4	85	79	85	172	144	HL6-11	Y	124	10	23	5	
NY	FL	4	85	79	85	172	144	HL6-11	Z	126	12	24	5	
NY	FL	4	85	79	85	172	150	HL6-20	A	60	22	33	6	
NY	FL	4	85	79	85	172	150	HL6-20	B	62	21	25	5	
NY	FL	4	85	79	85	172	150	HL6-20	C	63	12	23	5	

NY	FL	A1	84	171	85	172	103	HL5-18	A	57	9 <	18	6	
NY	FL	A1	84	171	85	172	103	HL5-18	B	65	9 <	19	6	
NY	FL	A1	84	171	85	172	103	HL5-18	C	63	9 <	18	6	
NY	FL	A1	84	171	85	172	103	HL5-18	Z	90	17	22	6	
NY	FL	A1	84	171	85	172	127	IL5-13	A	89	9 <	20	7	
NY	FL	A1	84	171	85	172	127	IL5-13	B	60	9 <	18	6	
NY	FL	A1	84	171	85	172	127	IL5-13	C	61	9 <	18	6	
NY	FL	A1	84	171	85	172	127	IL5-13	X	100	11	21	5	
NY	FL	A1	84	171	85	172	127	IL5-13	Y	110	15	20	4	
NY	FL	A1	84	171	85	172	127	IL5-13	Z	1100	20	21	7	
NY	FL	A1	84	171	85	172	136	GL5-08	A	53	9 <	16	5	
NY	FL	A1	84	171	85	172	136	GL5-08	B	63	9	19	6	
NY	FL	A1	84	171	85	172	136	GL5-08	C	67	10	23	5	
NY	FL	A2	85	172	86	177	N1	NA	A	80	15 <	20	10	AGG
NY	FL	A2	85	172	86	177	N2	NA	B	75	15 <	20	10	AGG
NY	FL	A2	85	172	86	177	N3	NA	C	70	15 <	20	5	AGG
NY	FL	A2	85	172	86	177	127	HL6-15	X	95	15 <	20	10	
NY	FL	A2	85	172	86	177	127	HL6-15	Y	100	15 <	20	10	
NY	FL	A2	85	172	86	177	127	HL6-15	Z	120	15 <	20	10	
NY	FL	A4	87	176	88	190	103	HL8-16	A	54	17 <	14	8 <	
NY	FL	A4	87	176	88	190	103	HL8-16	U	92	37	28	10	
NY	FL	A4	87	176	88	190	103	HL8-16	W	104	23	21	8	
NY	FL	A4	87	176	88	190	103	HL8-16	X	114	24	27	9	
NY	FL	A4	87	176	88	190	103	HL8-16	Y	168	24	27	10	
NY	FL	A4	87	176	88	190	103	HL8-16	Z	2300	44	23	10	
NY	FL	A4	87	176	88	190	127	GL6-17	A	52	17 <	16	8 <	
NY	FL	A4	87	176	88	190	127	GL6-17	X	127	18	19	9	
NY	FL	A4	87	176	88	190	127	GL6-17	Y	194	35	20	10	
NY	FL	A4	87	176	88	190	127	GL6-17	Z	3200	27	28	11	
NY	FL	A4	87	176	88	190	136	IL8-21	A	43	17 <	16	8	
NY	FL	A4	87	176	88	190	136	IL8-21	U	92	19	24	9	
NY	FL	A4	87	176	88	190	136	IL8-21	Z	2550	38	25	10	
NY	FL	B1	84	171	86	177	102	IU5-11	A	50	15 <	15	5 <	ICP
NY	FL	B1	84	171	86	177	102	IU5-11	B	60	15 <	20	5 <	ICP*
NY	FL	B1	84	171	86	177	102	IU5-11	C	60	15 <	20	5	ICP*
NY	FL	B1	84	171	86	177	102	IU5-11	Z	1298	27	22	8	
NY	FL	B1	84	171	86	177	139	HL4-19	A	55	15 <	20	5	ICP
NY	FL	B1	84	171	86	177	139	HL4-19	B	65	15 <	20	5	ICP*
NY	FL	B1	84	171	86	177	139	HL4-19	C	65	15 <	25	5	ICP*
NY	FL	B1	84	171	86	177	139	HL4-19	X	110	15 <	20	5	ICP
NY	FL	B1	84	171	86	177	139	HL4-19	Y	115	15 <	20	5	ICP
NY	FL	B1	84	171	86	177	139	HL4-19	Z	1130	15 <	20	10	ICP
NY	FL	B1	84	171	86	177	159	GL2-05	A	50	15 <	15	5	ICP
NY	FL	B1	84	171	86	177	159	GL2-05	B	60	15 <	20	5	ICP*
NY	FL	B1	84	171	86	177	159	GL2-05	C	60	15 <	20	5	ICP*
NY	FL	T1	84	171	87	176	128	HU4-21	A	59	7	14	5	
NY	FL	T1	84	171	87	176	128	HU4-21	X	340	29	34	19	
NY	FL	T1	84	171	87	176	128	HU4-21	Y	270	30	42	20	
NY	FL	T1	84	171	87	176	128	HU4-21	Z	6950	50	29	22	

NY	FL	T1	84	171	87	176	138	GU7-06	A	55	7	12	4	
NY	FL	T1	84	171	87	176	138	GU7-06	X	150	20	47	19	
NY	FL	T1	84	171	87	176	138	GU7-06	Y	215	20	28	15	
NY	FL	T1	84	171	87	176	138	GU7-06	Z	4610	30	28	19	
NY	FL	T1	84	171	87	176	148	IU2-14	A	53	7	12	4	
NY	FL	T1	84	171	87	176	148	IU2-14	X	170	20	50	20	
NY	FL	T1	84	171	87	176	148	IU2-14	Y	180	20	40	18	
NY	FL	T1	84	171	87	176	148	IU2-14	Z	2225	23	35	21	
NY	FL	Q1	84	171	88	190	124	HU5-08	A	40	17 <	18	8	
NY	FL	Q1	84	171	88	190	124	HU5-08	U	94	21	17	10	
NY	FL	Q1	84	171	88	190	124	HU5-08	Z	7005	23	20	22	
NY	FL	Q1	84	171	88	190	105	IL4-15	A	40	25	20	8	
NY	FL	Q1	84	171	88	190	105	IL4-15	U	74	17 <	14	10	
NY	FL	Q1	84	171	88	190	105	IL4-15	Z	228	17 <	16	13	
NY	FL	Q1	84	171	88	190	108	GL2-18	A	44	17 <	15	8	
NY	FL	Q1	84	171	88	190	108	GL2-18	X	75	17 <	26	7 <	
NY	FL	Q1	84	171	88	190	108	GL2-18	Z	231	31	23	13	
DC	FL	1	84	224	84	320	131	HU4-18	A	215	15 <	15	5 <	ICP
DC	FL	1	84	224	84	320	131	HU4-18	B	85	15 <	15	5 <	ICP
DC	FL	1	84	224	84	320	131	HU4-18	C	65	15 <	25	5 <	ICP
DC	FL	1	84	224	84	320	131	HU4-18	X	120	50	60	10	ICP
DC	FL	1	84	224	84	320	131	HU4-18	Y	340	55	60	10	ICP
DC	FL	1	84	224	84	320	131	HU4-18	Z	4920	91	65	15	ICP
DC	FL	1	84	224	84	320	144	GU1-11	A	200	15 <	15	5	ICP
DC	FL	1	84	224	84	320	144	GU1-11	B	75	15 <	20	5	ICP
DC	FL	1	84	224	84	320	144	GU1-11	C	70	15 <	20	5	ICP
DC	FL	1	84	224	84	320	150	HU4-04	A	320	15 <	15	5	ICP
DC	FL	1	84	224	84	320	150	HU4-04	B	90	15 <	15	5	ICP
DC	FL	1	84	224	84	320	150	HU4-04	C	70	15 <	15	5	ICP
DC	FL	1	84	224	84	320	150	HU4-04	X	320	95	53	6	
DC	FL	1	84	224	84	320	150	HU4-04	Y	863	100	53	7	
DC	FL	1	84	224	84	320	150	HU4-04	Z	5488	135	66	9	
DC	FL	2	84	320	85	45	131	GU4-22	A	126	15 <	18	6	
DC	FL	2	84	320	85	45	131	GU4-22	B	95	15 <	20	5 <	
DC	FL	2	84	320	85	45	131	GU4-22	C	98	15 <	20	5 <	
DC	FL	2	84	320	85	45	150	GU4-13	A	112	15 <	18	5 <	
DC	FL	2	84	320	85	45	150	GU4-13	B	100	15 <	21	5 <	
DC	FL	2	84	320	85	45	150	GU4-13	C	94	15 <	22	5 <	
DC	FL	2	84	320	85	45	144	HL6-10	A	110	15 <	16	5 <	
DC	FL	2	84	320	85	45	144	HL6-10	B	88	15 <	20	5 <	
DC	FL	2	84	320	85	45	144	HL6-10	C	84	15 <	19	5 <	
DC	FL	2	84	320	85	45	144	HL6-10	X	224	15 <	31	5	
DC	FL	2	84	320	85	45	144	HL6-10	Y	272	15 <	31	5	
DC	FL	2	84	320	85	45	144	HL6-10	Z	5408	16	33	5	
DC	FL	3	85	45	85	133	131	HL6-21	A	115	20	24	4	
DC	FL	3	85	45	85	133	131	HL6-21	B	96	14	25	4	
DC	FL	3	85	45	85	133	131	HL6-21	C	96	14	24	5	
DC	FL	3	85	45	85	133	144	GU4-15	A	95	15	24	4	

DC	FL	3	85	45	85	133	144	GU4-15	B	102	22	26	5
DC	FL	3	85	45	85	133	144	GU4-15	C	102	13	26	5
DC	FL	3	85	45	85	133	144	GU4-15	X	152	12	26	8
DC	FL	3	85	45	85	133	144	GU4-15	Y	173	18	28	6
DC	FL	3	85	45	85	133	144	GU4-15	Z	1410	18	27	6
DC	FL	3	85	45	85	133	150	HL6-03	A	93	14	19	4
DC	FL	3	85	45	85	133	150	HL6-03	B	90	10	20	4
DC	FL	3	85	45	85	133	150	HL6-03	C	89	10 <	21	4
DC	FL	4	85	133	85	224	131	GU4-12	A	150	21	23	4
DC	FL	4	85	133	85	224	131	GU4-12	B	83	27	24	4
DC	FL	4	85	133	85	224	131	GU4-12	C	70	16	27	4
DC	FL	4	85	133	85	224	144	GU4-07	A	159	20	20	4
DC	FL	4	85	133	85	224	144	GU4-07	B	82	14	24	4
DC	FL	4	85	133	85	224	144	GU4-07	C	71	14	22	4
DC	FL	4	85	133	85	224	144	GU4-07	X	995	206	115	10
DC	FL	4	85	133	85	224	144	GU4-07	Y	1202	226	124	11
DC	FL	4	85	133	85	224	144	GU4-07	Z	4960	235	127	11
DC	FL	4	85	133	85	224	150	HL6-18	A	158	17	18	4
DC	FL	4	85	133	85	224	150	HL6-18	B	72	22	21	4
DC	FL	4	85	133	85	224	150	HL6-18	C	63	16	20	4
DC	FL	13	87	231	87	318	131	GL6-10	A	111	12	16	9 <
DC	FL	13	87	231	87	318	131	GL6-10	X	178	22	34	9 <
DC	FL	13	87	231	87	318	131	GL6-10	Y	300	17	32	10
DC	FL	13	87	231	87	318	131	GL6-10	Z	5000	10 <	32	9
DC	FL	13	87	231	87	318	144	HL8-03	A	97	10 <	26	9 <
DC	FL	13	87	231	87	318	144	HL8-03	X	276	12	37	9 <
DC	FL	13	87	231	87	318	144	HL8-03	Y	268	13	40	9
DC	FL	13	87	231	87	318	144	HL8-03	Z	3400	12	31	9 <
DC	FL	13	87	231	87	318	150	GL6-23	A	90	13	19	9 <
DC	FL	13	87	231	87	318	150	GL6-23	X	198	11	29	9 <
DC	FL	13	87	231	87	318	150	GL6-23	Y	257	12	31	9
DC	FL	13	87	231	87	318	150	GL6-23	Z	3100	13	28	9
DC	FL	14	87	318	88	48	131	HL8-13	A	93	10 <	27	9 <
DC	FL	14	87	318	88	48	131	HL8-13	X	207	12	30	9
DC	FL	14	87	318	88	48	131	HL8-13	Y	408	11	28	10
DC	FL	14	87	318	88	48	131	HL8-13	Z	7100	11	40	10
DC	FL	14	87	318	88	48	144	GL3-15	A	106	10 <	15	16
DC	FL	14	87	318	88	48	144	GL3-15	X	354	18	28	9
DC	FL	14	87	318	88	48	144	GL3-15	Y	253	12	42	10
DC	FL	14	87	318	88	48	144	GL3-15	Z	6030	16	24	10
DC	FL	14	87	318	88	48	150	HL8-10	A	93	10 <	23	9 <
DC	FL	14	87	318	88	48	150	HL8-10	X	283	10	34	29
DC	FL	14	87	318	88	48	150	HL8-10	Y	285	10	38	22
DC	FL	14	87	318	88	48	150	HL8-10	Z	6400	13	25	10
DC	FL	15	88	48	88	160	131	GL3-13	A	207	42	24	10 <
DC	FL	15	88	48	88	160	131	GL3-13	X	489	249	150	10 <
DC	FL	15	88	48	88	160	131	GL3-13	Y	643	243	145	10 <
DC	FL	15	88	48	88	160	131	GL3-13	Z	6710	279	172	10 <
DC	FL	15	88	48	88	160	144	HL2-02	A	256	42	22	10 <

DC	FL	15	88	48	88	160	144	HL2-02	X	476	270	132	10 <	
DC	FL	15	88	48	88	160	144	HL2-02	Y	1040	271	140	10 <	
DC	FL	15	88	48	88	160	144	HL2-02	Z	9260	292	137	10 <	
DC	FL	15	88	48	88	160	150	GL6-24	A	283	40	23	10 <	
DC	FL	15	88	48	88	160	150	GL6-24	X	327	230	164	10 <	
DC	FL	15	88	48	88	160	150	GL6-24	Y	580	248	142	10 <	
DC	FL	15	88	48	88	160	150	GL6-24	Z	8180	305	170	10 <	
DC	FL	16	88	180	88	258	131	GL8-01	Z	890	108	62	7 <	
DC	FL	16	88	180	88	258	144	GL8-15	Z	631	124	49	7 <	
DC	FL	16	88	180	88	258	150	GL8-24	Z	1015	153	91	7 <	
DC	FL	A1	84	224	85	224	103	HL4-15	A	163	24	20	4	
DC	FL	A1	84	224	85	224	103	HL4-15	B	82	15	22	4	
DC	FL	A1	84	224	85	224	103	HL4-15	C	73	9	20	4	
DC	FL	A1	84	224	85	224	127	IL5-08	A	181	21	19	4	
DC	FL	A1	84	224	85	224	127	IL5-08	B	84	14	21	4	
DC	FL	A1	84	224	85	224	127	IL5-08	C	69	12	21	4	
DC	FL	A1	84	224	85	224	127	IL5-08	X	480	365	86	8	
DC	FL	A1	84	224	85	224	127	IL5-08	Y	940	385	90	8	
DC	FL	A1	84	224	85	224	127	IL5-08	Z	14170	475	102	8	
DC	FL	A1	84	224	85	224	136	GL5-17	A	129	18	23	4	
DC	FL	A1	84	224	85	224	136	GL5-17	B	83	17	26	4	
DC	FL	A1	84	224	85	224	136	GL5-17	C	76	11	25	4	
DC	FL	A1	84	224	85	224	136	GL5-17	Z	14200	631	132	18	
DC	FL	A2	85	224	86	226	N1	NA	A	260	45	30	5	AGG
DC	FL	A2	85	224	86	226	N2	NA	B	85	15	35	5	AGG
DC	FL	A2	85	224	86	226	N3	NA	C	85	15 <	25	5	AGG
DC	FL	A2	85	224	86	226	127	GL5-20	X	715	580	110	10	
DC	FL	A2	85	224	86	226	127	GL5-20	Y	1370	600	105	10	
DC	FL	A2	85	224	86	226	127	GL5-20	Z	9870	705	120	15	
DC	FL	A4	87	223	88	258	103	GL6-21	A	173	40	22	7 <	
DC	FL	A4	87	223	88	258	103	GL6-21	U	327	665	129	7 <	
DC	FL	A4	87	223	88	258	103	GL6-21	Z	16900	783	180	7	
DC	FL	A4	87	223	88	258	127	HL8-07	A	217	32	20	7 <	
DC	FL	A4	87	223	88	258	127	HL8-07	X	439	615	123	7 <	
DC	FL	A4	87	223	88	258	127	HL8-07	Z	20700	771	114	7 <	
DC	FL	A4	87	223	88	258	136	GL6-03	A	204	40	21	7 <	
DC	FL	A4	87	223	88	258	136	GL6-03	U	198	671	179	7 <	
DC	FL	A4	87	223	88	258	136	GL6-03	Z	17700	821	187	9	
DC	FL	B1	84	224	86	226	102	IU5-15	A	305	55	20	5	ICP
DC	FL	B1	84	224	86	226	102	IU5-15	B	95	15 <	20	5	ICP*
DC	FL	B1	84	224	86	226	102	IU5-15	C	90	15 <	20	5	ICP*
DC	FL	B1	84	224	86	226	102	IU5-15	Z	14800	61	90	18	
DC	FL	B1	84	224	86	226	139	HL4-10	A	240	40	20	5	ICP
DC	FL	B1	84	224	86	226	139	HL4-10	B	95	15 <	20	5	ICP*
DC	FL	B1	84	224	86	226	139	HL4-10	C	95	15 <	15	5	ICP*
DC	FL	B1	84	224	86	226	139	HL4-10	X	1020	645	105	10	ICP
DC	FL	B1	84	224	86	226	139	HL4-10	Y	2180	865	110	10	ICP
DC	FL	B1	84	224	86	226	139	HL4-10	Z	19900	960	155	15	ICP
DC	FL	B1	84	224	86	226	159	GL2-06	A	230	30	20	5	ICP

DC	FL	B1	84	224	86	226	159	GL2-06	B	90	15 <	20	5 <	ICP*
DC	FL	B1	84	224	86	226	159	GL2-06	C	80	15 <	15	5	ICP*
DC	FL	T1	84	224	87	223	128	HU4-15	A	325	70	45	6	
DC	FL	T1	84	224	87	223	128	HU4-15	X	890	585	80	10	
DC	FL	T1	84	224	87	223	128	HU4-15	Y	2395	550	105	15	
DC	FL	T1	84	224	87	223	128	HU4-15	Z	29000	850	120	50	
DC	FL	T1	84	224	87	223	138	GU7-01	A	295	65	35	8	
DC	FL	T1	84	224	87	223	138	GU7-01	X	1610	105	40	10	
DC	FL	T1	84	224	87	223	138	GU7-01	Y	8310	140	35	10	
DC	FL	T1	84	224	87	223	138	GU7-01	Z	43000	345	50	60	
DC	FL	T1	84	224	87	223	148	IU2-11	A	290	60	40	6	
DC	FL	T1	84	224	87	223	148	IU2-11	X	695	355	70	10	
DC	FL	T1	84	224	87	223	148	IU2-11	Y	2660	390	70	10	
DC	FL	T1	84	224	87	223	148	IU2-11	Z	30000	550	75	40	
DC	FL	Q1	84	224	88	258	124	HU5-20	A	178	40	18	7 <	
DC	FL	Q1	84	224	88	258	124	HU5-20	U	140	148	44	10	
DC	FL	Q1	84	224	88	258	124	HU5-20	Z	42000	518	54	27	
DC	FL	Q1	84	224	88	258	105	IL4-05	A	184	42	20	9	
DC	FL	Q1	84	224	88	258	105	IL4-05	U	190	194	44	7 <	
DC	FL	Q1	84	224	88	258	105	IL4-05	Z	47200	608	53	30	
DC	FL	Q1	84	224	88	258	108	GL2-09	A	222	27	22	7 <	
DC	FL	Q1	84	224	88	258	108	GL2-09	X	596	424	77	10	
DC	FL	Q1	84	224	88	258	108	GL2-09	Z	26200	642	78	25	
CH	FL	9	86	198	86	293	131	GL3-14	A	267	11	18	6	
CH	FL	9	86	198	86	293	131	GL3-14	X	350	20	41	12	
CH	FL	9	86	198	86	293	131	GL3-14	Y	530	21	46	14	
CH	FL	9	86	198	86	293	131	GL3-14	Z	7500	25	42	14	
CH	FL	9	86	198	86	293	144	HL2-22	A	241	13	19	5	
CH	FL	9	86	198	86	293	144	HL2-22	X	340	31	75	21	
CH	FL	9	86	198	86	293	144	HL2-22	Y	600	29	64	18	
CH	FL	9	86	198	86	293	144	HL2-22	Z	7300	29	52	14	
CH	FL	9	86	198	86	293	150	IL8-01	A	209	9	18	5	
CH	FL	9	86	198	86	293	150	IL8-01	X	360	28	40	13	
CH	FL	9	86	198	86	293	150	IL8-01	Y	745	29	60	20	
CH	FL	9	86	198	86	293	150	IL8-01	Z	11000	29	44	14	
CH	FL	10	86	293	87	33	131	IL8-20	A	173	13	18	5	
CH	FL	10	86	293	87	33	131	IL8-20	X	317	35	120	20	
CH	FL	10	86	293	87	33	131	IL8-20	Y	410	86	120	22	
CH	FL	10	86	293	87	33	131	IL8-20	Z	7500	103	88	15	
CH	FL	10	86	293	87	33	144	GL3-02	A	163	16	16	5	
CH	FL	10	86	293	87	33	144	GL3-02	X	450	60	101	18	
CH	FL	10	86	293	87	33	144	GL3-02	Y	505	62	92	16	
CH	FL	10	86	293	87	33	144	GL3-02	Z	5625	70	87	8	
CH	FL	10	86	293	87	33	150	HL2-21	A	146	12	21	5	
CH	FL	10	86	293	87	33	150	HL2-21	X	366	65	105	14	
CH	FL	10	86	293	87	33	150	HL2-21	Y	500	67	105	16	
CH	FL	10	86	293	87	33	150	HL2-21	Z	7100	73	98	16	
CH	FL	11	87	33	87	111	131	HL2-16	A	214	12	20	5	

CH	FL	11	87	33	87 111	131	HL2-16	X	420	38	101	24
CH	FL	11	87	33	87 111	131	HL2-16	Y	6275	34	74	17
CH	FL	11	87	33	87 111	131	HL2-16	Z	7800	42	65	16
CH	FL	11	87	33	87 111	144	IL8-04	A	206	14	18	5
CH	FL	11	87	33	87 111	144	IL8-04	X	420	30	62	15
CH	FL	11	87	33	87 111	144	IL8-04	Y	440	31	67	14
CH	FL	11	87	33	87 111	144	IL8-04	Z	7550	38	64	15
CH	FL	12	87	111	87 209	131	GL3-21	A	665	20	25	8
CH	FL	12	87	111	87 209	131	GL3-21	X	355	125	80	8
CH	FL	12	87	111	87 209	131	GL3-21	Y	740	120	75	9
CH	FL	12	87	111	87 209	131	GL3-21	Z	9680	140	85	10
CH	FL	12	87	111	87 209	144	GL3-18	A	570	20	30	7
CH	FL	12	87	111	87 209	144	GL3-18	X	260	120	75	8
CH	FL	12	87	111	87 209	144	GL3-18	Y	355	120	70	8
CH	FL	12	87	111	87 209	144	GL3-18	Z	8140	135	75	10
CH	FL	12	87	111	87 209	150	HL2-11	A	524	20	30	8
CH	FL	12	87	111	87 209	150	HL2-11	X	410	120	70	8
CH	FL	12	87	111	87 209	150	HL2-11	Y	515	120	70	8
CH	FL	12	87	111	87 209	150	HL2-11	Z	6920	125	70	9
CH	FL	A3	86	198	87 209	103	HL2-23	A	570	20	30	8
CH	FL	A3	86	198	87 209	103	HL2-23	B	175	15	25	5
CH	FL	A3	86	198	87 209	103	HL2-23	C	135	15	30	5
CH	FL	A3	86	198	87 209	103	HL2-23	X	650	145	50	10
CH	FL	A3	86	198	87 209	103	HL2-23	Y	1180	140	60	10
CH	FL	A3	86	198	87 209	103	HL2-23	Z	20000	160	55	15
CH	FL	A3	86	198	87 209	127	IL8-05	A	550	15	30	7
CH	FL	A3	86	198	87 209	127	IL8-05	X	495	115	50	9
CH	FL	A3	86	198	87 209	127	IL8-05	Y	1170	115	60	9
CH	FL	A3	86	198	87 209	127	IL8-05	Z	18000	150	50	15
CH	FL	A3	86	198	87 209	136	GL3-16	A	555	15	30	7
CH	FL	A3	86	198	87 209	136	GL3-16	X	335	115	55	9
CH	FL	A3	86	198	87 209	136	GL3-16	Y	810	110	55	10
CH	FL	A3	86	198	87 209	136	GL3-16	Z	17000	125	55	15
CH	FL	A4	87	209	88 223	103	HL2-09	A	353	17 <	17	10
CH	FL	A4	87	209	88 223	103	HL2-09	U	387	235	97	11
CH	FL	A4	87	209	88 223	103	HL2-09	Z	23600	271	113	15
CH	FL	A4	87	209	88 223	127	HL8-04	A	296	21	18	10
CH	FL	A4	87	209	88 223	127	HL8-04	X	361	210	103	11
CH	FL	A4	87	209	88 223	127	HL8-04	Z	11800	261	118	13
CH	FL	A4	87	209	88 223	136	IL8-12	A	260	17 <	21	8
CH	FL	A4	87	209	88 223	136	IL8-12	U	308	249	103	10
CH	FL	A4	87	209	88 223	136	IL8-12	Z	21400	210	117	12
CH	FL	B2	86	198	88 223	139	GL3-05	A	314	35	23	8
CH	FL	B2	86	198	88 223	139	GL3-05	X	486	148	60	11
CH	FL	B2	86	198	88 223	139	GL3-05	Z	28200	212	60	26
CH	FL	B2	86	198	88 223	102	IL8-03	A	310	20	14	8
CH	FL	B2	86	198	88 223	102	IL8-03	X	775	168	60	10
CH	FL	B2	86	198	88 223	102	IL8-03	Z	29000	241	58	21
CH	FL	B2	86	198	88 223	159	HL2-14	A	338	17 <	18	8

CH	FL	B2	86	198	88	223	159	HL2-14	X	593	178	80	11
CH	FL	B2	86	198	88	223	159	HL2-14	Z	31000	228	62	26
OHM	DFL	A4	87	209	88	223	356	GL6-05	A	2580	28	25	14
OHM	DFL	A4	87	209	88	223	356	GL6-05	U	556	145	130	8
OHM	DFL	A4	87	209	88	223	356	GL6-05	Z	14400	193	158	28
OHM	DFL	A4	87	209	88	223	379	HL2-04	A	257	40	26	16
OHM	DFL	A4	87	209	88	223	379	HL2-04	U	554	144	134	8
OHM	DFL	A4	87	209	88	223	379	HL2-04	Z	7850	176	162	22
OHM	SFL	A4	87	209	88	223	304	GL6-06	A	383	18	17	12
OHM	SFL	A4	87	209	88	223	304	GL6-06	U	738	144	145	8
OHM	SFL	A4	87	209	88	223	304	GL6-06	Z	12900	169	179	25
OHM	SFL	A4	87	209	88	223	326	HL2-10	A	455	28	23	10
OHM	SFL	A4	87	209	88	223	326	HL2-10	U	820	203	188	9
OHM	SFL	A4	87	209	88	223	326	HL2-10	Z	15800	243	202	16

MARBLE ANION CONCENTRATIONS / 1984-1988

SITE	MAT	PER	SYR	SJD	EYR	EJD	SLOT	SAMPLE	LAY	SO4 DS	NO3 DN	CL DC	FL DF	COMMENTS
=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====	=====
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	NA	15 <	15 <	5	5 <	BULK
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	NA	15 <	15 <	9	5 <	BULK
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	NA	15 <	15 <	4	5 <	BULK
CB	FM	NA	NA	NA	NA	NA	N1	H36-12	A	15 <	15 <	5	5	ICP
CB	FM	NA	NA	NA	NA	NA	N1	H36-12	B	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	H36-12	C	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	A	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	B	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	C	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	X	15 <	15 <	4	5 <	
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	Y	15 <	15 <	4	5 <	
CB	FM	NA	NA	NA	NA	NA	N1	I11-13	Z	15 <	15 <	4	5 <	
CB	FM	NA	NA	NA	NA	NA	N1	N15-20	A	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	N15-20	B	15 <	15 <	5 <	5 <	ICP
CB	FM	NA	NA	NA	NA	NA	N1	N15-20	C	15 <	15 <	5 <	5 <	ICP
NC	FM	1	84	146	84	237	231	N15-01	A	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	231	N15-01	B	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	231	N15-01	C	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	231	N15-01	Z	240	41	12	2	
NC	FM	1	84	146	84	237	244	K36-17	A	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	244	K36-17	B	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	244	K36-17	C	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	244	K36-17	X	22	10	5	2 <	
NC	FM	1	84	146	84	237	244	K36-17	Y	26	12	4	2	
NC	FM	1	84	146	84	237	244	K36-17	Z	456	64	10	5	
NC	FM	1	84	146	84	237	250	C16-11	A	15 <	15 <	5	10 <	ICP
NC	FM	1	84	146	84	237	250	C16-11	B	15 <	15 <	5 <	10 <	ICP
NC	FM	1	84	146	84	237	250	C16-11	C	15 <	15 <	5 <	10 <	ICP
NC	FM	2	84	237	84	331	231	H14-20	A	25	15 <	3	5 <	
NC	FM	2	84	237	84	331	231	H14-20	B	15 <	15 <	3	5 <	
NC	FM	2	84	237	84	331	231	H14-20	C	15 <	15 <	4	5 <	
NC	FM	2	84	237	84	331	244	I14-04	A	38	15 <	7	6	
NC	FM	2	84	237	84	331	244	I14-04	B	15 <	15 <	5	5 <	
NC	FM	2	84	237	84	331	244	I14-04	C	15 <	15 <	5	5 <	
NC	FM	2	84	237	84	331	244	I14-04	X	18	8 <	4	3 <	
NC	FM	2	84	237	84	331	244	I14-04	Y	44	8	5	3 <	
NC	FM	2	84	237	84	331	244	I14-04	Z	665	33	8	3	
NC	FM	2	84	237	84	331	250	H11-08	A	31	15 <	7	5 <	
NC	FM	2	84	237	84	331	250	H11-08	B	15 <	15 <	6	5 <	
NC	FM	2	84	237	84	331	250	H11-08	C	15 <	15 <	6	5 <	
NC	FM	3	84	331	85	60	231	K26-11	A	10 <	10 <	3	2 <	
NC	FM	3	84	331	85	60	231	K26-11	B	11	10 <	3	2 <	
NC	FM	3	84	331	85	60	231	K26-11	C	10 <	10 <	5	2 <	
NC	FM	3	84	331	85	60	244	C16-01	A	10 <	10 <	4	2 <	
NC	FM	3	84	331	85	60	244	C16-01	B	10 <	10 <	3 <	2 <	

NC	FM	3	84 331	85 60	244 C16-01	C	10 <	10 <	3	2 <	
NC	FM	3	84 331	85 60	250 K26-03	A	11	10 <	4	2 <	
NC	FM	3	84 331	85 60	250 K26-03	B	11	10 <	7	2 <	
NC	FM	3	84 331	85 60	250 K26-03	C	10 <	10 <	3	2 <	
NC	FM	3	84 331	85 60	250 K26-03	X	27	16	5	2 <	
NC	FM	3	84 331	85 60	250 K26-03	Y	41	18	6	2 <	
NC	FM	3	84 331	85 60	250 K26-03	Z	458	47	8	2	
NC	FM	4	85 60	85 136	231 L15-09	A	10 <	10 <	5	2 <	
NC	FM	4	85 60	85 136	231 L15-09	B	10 <	10 <	5	2 <	
NC	FM	4	85 60	85 136	231 L15-09	C	10 <	10 <	4	2 <	
NC	FM	4	85 60	85 136	244 K26-02	A	10	10 <	4	2 <	
NC	FM	4	85 60	85 136	244 K26-02	B	10 <	10 <	3	2 <	
NC	FM	4	85 60	85 136	244 K26-02	C	10 <	10 <	3	2 <	
NC	FM	4	85 60	85 136	244 K26-02	X	27	10	6	2 <	
NC	FM	4	85 60	85 136	244 K26-02	Y	25	10	4	2 <	
NC	FM	4	85 60	85 136	244 K26-02	Z	534	59	15	3	
NC	FM	4	85 60	85 136	250 L15-23	A	17	13	7	2 <	
NC	FM	4	85 60	85 136	250 L15-23	B	10 <	10 <	5	2 <	
NC	FM	4	85 60	85 136	250 L15-23	C	10 <	10 <	4	2 <	
NC	FM	5	85 136	85 240	N1 NA	A	20 <	15 <	10	5 <	AGG
NC	FM	5	85 136	85 240	N1 NA	Z	375	35	10	5	AGG
NC	FM	6	85 240	85 331	N1 NA	A	30	15 <	5 <	5 <	AGG
NC	FM	6	85 240	85 331	N1 NA	Z	255	25	5	5	AGG
NC	FM	7	85 331	86 62	N1 NA	A	40	30	10	5 <	AGG
NC	FM	7	85 331	86 62	N1 NA	Z	445	25	15	5	AGG
NC	FM	8	86 62	86 155	N1 NA	A	35	15 <	5	5 <	AGG
NC	FM	8	86 62	86 155	N1 NA	Z	345	70	10	5	AGG
NC	FM	A1	84 146	85 136	203 I36-17	A	10	8 <	4	2 <	ICP
NC	FM	A1	84 146	85 136	203 I36-17	B	14	8 <	4	2 <	ICP
NC	FM	A1	84 146	85 136	203 I36-17	C	8	8 <	3	2 <	ICP
NC	FM	A1	84 146	85 136	203 I36-17	X	42	17	7	4	ICP
NC	FM	A1	84 146	85 136	203 I36-17	Y	87	15	7	4	ICP
NC	FM	A1	84 146	85 136	203 I36-17	Z	2477	58	11	10	ICP
NC	FM	A1	84 146	85 136	227 K36-06	A	9	8 <	4	2 <	ICP
NC	FM	A1	84 146	85 136	227 K36-06	B	8 <	8 <	3	2 <	ICP
NC	FM	A1	84 146	85 136	227 K36-06	C	8 <	8 <	4	2 <	ICP
NC	FM	A1	84 146	85 136	227 K36-06	Z	2974	71	15	19	
NC	FM	A1	84 146	85 136	236 E26-12	A	8	8 <	5	2 <	ICP
NC	FM	A1	84 146	85 136	236 E26-12	B	8 <	8 <	4	2 <	ICP
NC	FM	A1	84 146	85 136	236 E26-12	C	8 <	8 <	5	2 <	ICP
NC	FM	A2	85 136	86 155	N1 NA	A	35	15 <	10	5 <	AGG
NC	FM	A2	85 136	86 155	N2 NA	B	20 <	15 <	5	5 <	AGG
NC	FM	A2	85 136	86 155	N3 NA	C	30	15 <	5	5 <	AGG
NC	FM	A2	85 136	86 155	236 L15-05	X	80	15	10	5 <	
NC	FM	A2	85 136	86 155	236 L15-05	Y	120	15 <	10	5 <	
NC	FM	A2	85 136	86 155	236 L15-05	Z	1570	50	10	10	
NC	FM	A4	87 160	88 188	203 K14-18	A	30	17 <	8 <	8 <	
NC	FM	A4	87 160	88 188	203 K14-18	Z	1440	98	10	12	
NC	FM	A4	87 160	88 188	227 G34-24	A	28	17 <	8 <	8 <	

NC	FM	A4	87 160	88 188	227 G34-24	Z	1320	67	9	11	
NC	FM	A4	87 160	88 188	236 G24-18	A	32	17 <	10	8 <	
NC	FM	A4	87 160	88 188	236 G24-18	Z	1340	61	10	11	
NC	FM	B1	84 146	86 155	202 K36-01	A	25	15 <	5	5 <	ICP
NC	FM	B1	84 146	86 155	202 K36-01	B	20 <	15 <	5	5 <	
NC	FM	B1	84 146	86 155	202 K36-01	C	20 <	15 <	5 <	5 <	
NC	FM	B1	84 146	86 155	202 K36-01	Z	2435	31	12	22	
NC	FM	B1	84 146	86 155	239 I36-07	A	20 <	15 <	10	5 <	ICP
NC	FM	B1	84 146	86 155	239 I36-07	B	30	15 <	20	5 <	
NC	FM	B1	84 146	86 155	239 I36-07	C	20 <	15 <	5	5 <	
NC	FM	B1	84 146	86 155	259 E26-01	A	20 <	15 <	5	5 <	ICP
NC	FM	B1	84 146	86 155	259 E26-01	B	20 <	15 <	5	5 <	
NC	FM	B1	84 146	86 155	259 E26-01	C	20 <	15 <	5	5 <	
NC	FM	B1	84 146	86 155	259 E26-01	X	65	15 <	10	5 <	
NC	FM	B1	84 146	86 155	259 E26-01	Y	90	15 <	10	5 <	
NC	FM	B1	84 146	86 155	259 E26-01	Z	3110	45	15	20	ICP
NC	FM	T1	84 146	87 160	228 N15-13	A	23	18	4	2 <	
NC	FM	T1	84 146	87 160	228 N15-13	X	27	22	4	2 <	
NC	FM	T1	84 146	87 160	228 N15-13	Y	72	27	6	2 <	
NC	FM	T1	84 146	87 160	228 N15-13	Z	4894	15	20	44	
NC	FM	T1	84 146	87 160	238 K36-07	A	21	16	4 <	2 <	
NC	FM	T1	84 146	87 160	238 K36-07	X	28	29	8	2 <	
NC	FM	T1	84 146	87 160	238 K36-07	Y	92	34	6	2 <	
NC	FM	T1	84 146	87 160	238 K36-07	Z	1763	130	15	14	
NC	FM	T1	84 146	87 160	248 C16-07	A	26	15	5	2 <	
NC	FM	T1	84 146	87 160	248 C16-07	X	54	35	7	2 <	
NC	FM	T1	84 146	87 160	248 C16-07	Y	83	37	6	3	
NC	FM	T1	84 146	87 160	248 C16-07	Z	3568	130	16	29	
NC	FM	Q1	84 146	88 188	224 N15-08	A	32	17 <	8	8 <	
NC	FM	Q1	84 146	88 188	224 N15-08	X	40	39	8	8 <	
NC	FM	Q1	84 146	88 188	224 N15-08	Y	90	25	8 <	8 <	
NC	FM	Q1	84 146	88 188	224 N15-08	Z	5520	78	10	39	
NC	FM	Q1	84 146	88 188	205 C16-24	A	25	24	8 <	8 <	
NC	FM	Q1	84 146	88 188	205 C16-24	X	97	37	10	8 <	
NC	FM	Q1	84 146	88 188	205 C16-24	Y	170	39	8	8 <	
NC	FM	Q1	84 146	88 188	205 C16-24	Z	3060	48	8	22	
NC	FM	Q1	84 146	88 188	208 K36-12	A	24	17 <	8 <	8 <	
NC	FM	Q1	84 146	88 188	208 K36-12	X	49	27	8	8 <	
NC	FM	Q1	84 146	88 188	208 K36-12	Y	80	44	11	8 <	
NC	FM	Q1	84 146	88 188	208 K36-12	Z	1350	80	12	18	
NJ	FM	1	84 157	84 251	231 I11-01	A	20	15 <	5 <	10 <	ICP
NJ	FM	1	84 157	84 251	231 I11-01	B	15 <	15 <	5 <	10 <	ICP
NJ	FM	1	84 157	84 251	231 I11-01	C	15 <	15 <	5 <	10 <	ICP
NJ	FM	1	84 157	84 251	231 I11-01	X	30	18	5	2	
NJ	FM	1	84 157	84 251	231 I11-01	Y	35	17	6	2	
NJ	FM	1	84 157	84 251	231 I11-01	Z	624	48	9	3	
NJ	FM	1	84 157	84 251	244 G36-12	A	15 <	15 <	5 <	10 <	ICP
NJ	FM	1	84 157	84 251	244 G36-12	B	15 <	15 <	5 <	5 <	ICP

NJ	FM	1	84	157	84	251	244	G36-12	C	15 <	15 <	5 <	5 <	ICP
NJ	FM	1	84	157	84	251	250	G26-21	A	35	15 <	5	10 <	ICP
NJ	FM	1	84	157	84	251	250	G26-21	B	15 <	15 <	5	10 <	ICP
NJ	FM	1	84	157	84	251	250	G26-21	C	15 <	15 <	5	10 <	ICP
NJ	FM	2	84	251	84	349	231	I14-14	A	33	15 <	3 <	5 <	
NJ	FM	2	84	251	84	349	231	I14-14	B	15 <	15 <	3 <	5 <	
NJ	FM	2	84	251	84	349	231	I14-14	C	15 <	15 <	3 <	5 <	
NJ	FM	2	84	251	84	349	244	I14-23	A	32	15 <	3	5 <	
NJ	FM	2	84	251	84	349	244	I14-23	B	15 <	15 <	3 <	5 <	
NJ	FM	2	84	251	84	349	244	I14-23	C	15 <	15 <	3 <	5 <	
NJ	FM	2	84	251	84	349	244	I14-23	X	32	15 <	2	2	
NJ	FM	2	84	251	84	349	244	I14-23	Y	50	15 <	2	2	
NJ	FM	2	84	251	84	349	244	I14-23	Z	1185	55	9	3	
NJ	FM	2	84	251	84	349	250	K36-02	A	36	15 <	4	5 <	
NJ	FM	2	84	251	84	349	250	K36-02	B	15 <	15 <	5	5 <	
NJ	FM	2	84	251	84	349	250	K36-02	C	15 <	15 <	3	5 <	
NJ	FM	3	84	349	85	65	231	K26-01	A	33	34	10	2 <	
NJ	FM	3	84	349	85	65	231	K26-01	B	10 <	14	6	2 <	
NJ	FM	3	84	349	85	65	231	K26-01	C	10 <	12	5	2 <	
NJ	FM	3	84	349	85	65	244	E26-17	A	32	25	8	2 <	
NJ	FM	3	84	349	85	65	244	E26-17	B	12	13	5	2 <	
NJ	FM	3	84	349	85	65	244	E26-17	C	10 <	10 <	4	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	A	32	25	8	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	B	10 <	13	5	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	C	10 <	16	6	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	X	42	27	10	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	Y	74	31	12	2 <	
NJ	FM	3	84	349	85	65	250	K26-18	Z	1000	99	29	4	
NJ	FM	4	85	65	85	158	231	L15-06	A	22	20	5	2 <	
NJ	FM	4	85	65	85	158	231	L15-06	B	15	10	4	2 <	
NJ	FM	4	85	65	85	158	231	L15-06	C	16	10 <	5	2 <	
NJ	FM	4	85	65	85	158	244	L15-16	A	24	16	5	2 <	
NJ	FM	4	85	65	85	158	244	L15-16	B	14	10 <	4	2 <	
NJ	FM	4	85	65	85	158	244	L15-16	C	11	10 <	5	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	A	17	15	3 <	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	B	14	10 <	4	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	C	15	10 <	3	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	X	44	28	6	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	Y	83	31	22	2 <	
NJ	FM	4	85	65	85	158	250	K26-06	Z	856	104	11	2	
NJ	FM	A1	84	157	85	158	203	I11-02	A	19	15	5	3	
NJ	FM	A1	84	157	85	158	203	I11-02	B	9 <	10	4	2	
NJ	FM	A1	84	157	85	158	203	I11-02	C	9 <	9 <	4	3	
NJ	FM	A1	84	157	85	158	203	I11-02	Z	2717	94	16	9	
NJ	FM	A1	84	157	85	158	227	I36-13	A	15	12	4	3	
NJ	FM	A1	84	157	85	158	227	I36-13	B	10	15	6	3	
NJ	FM	A1	84	157	85	158	227	I36-13	C	9 <	9 <	4	2	
NJ	FM	A1	84	157	85	158	227	I36-13	X	95	29	7	2	
NJ	FM	A1	84	157	85	158	227	I36-13	Y	135	32	7	1	

NJ	FM	A1	84 157	85 158	227	I36-13	Z	2745	96	15	7	
NJ	FM	A1	84 157	85 158	236	I14-24	A	16	15	4	2	
NJ	FM	A1	84 157	85 158	236	I14-24	B	10	10	4	3	
NJ	FM	A1	84 157	85 158	236	I14-24	C	11	9 <	4	3	
NJ	FM	A2	85 158	86 169	N1	NA	A	25	15 <	5	5 <	AGG
NJ	FM	A2	85 158	86 169	N2	NA	B	20 <	15 <	5	5 <	AGG
NJ	FM	A2	85 158	86 169	N3	NA	C	20 <	15 <	5	5 <	AGG
NJ	FM	A2	85 158	86 169	236	K26-20	X	80	30	10	5 <	
NJ	FM	A2	85 158	86 169	236	K26-20	Y	145	45	15	5 <	
NJ	FM	A2	85 158	86 169	236	K26-20	Z	2030	70	10	10	
NJ	FM	B1	84 157	86 169	202	H36-23	A	40	15 <	10	5 <	ICP
NJ	FM	B1	84 157	86 169	202	H36-23	B	20	15 <	5	5 <	
NJ	FM	B1	84 157	86 169	202	H36-23	C	20 <	15 <	5	5 <	
NJ	FM	B1	84 157	86 169	202	H36-23	Z	821	42	12	3	
NJ	FM	B1	84 157	86 169	239	I11-03	A	30	20	10	5 <	ICP
NJ	FM	B1	84 157	86 169	239	I11-03	B	20 <	15 <	5	5 <	
NJ	FM	B1	84 157	86 169	239	I11-03	C	20 <	15 <	5 <	5 <	
NJ	FM	B1	84 157	86 169	259	H36-08	A	40	25	5	5 <	ICP
NJ	FM	B1	84 157	86 169	259	H36-08	B	20	15 <	5	5 <	
NJ	FM	B1	84 157	86 169	259	H36-08	C	25	15 <	5	5 <	
NJ	FM	B1	84 157	86 169	259	H36-08	X	185	25	10	5 <	
NJ	FM	B1	84 157	86 169	259	H36-08	Y	300	25	10	5 <	
NJ	FM	B1	84 157	86 169	259	H36-08	Z	4940	95	15	15	ICP
NY	FM	1	84 171	84 269	231	I11-05	A	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	231	I11-05	B	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	231	I11-05	C	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	231	I11-05	X	16	12 <	3	2 <	
NY	FM	1	84 171	84 269	231	I11-05	Y	18	12 <	10	2	
NY	FM	1	84 171	84 269	231	I11-05	Z	275	26	8	2	
NY	FM	1	84 171	84 269	244	G36-13	A	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	244	G36-13	B	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	244	G36-13	C	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	250	I36-08	A	15 <	15 <	12	5 <	ICP
NY	FM	1	84 171	84 269	250	I36-08	B	15 <	15 <	5 <	5 <	ICP
NY	FM	1	84 171	84 269	250	I36-08	C	15 <	15 <	5 <	5 <	ICP
NY	FM	2	84 269	84 356	231	I14-10	A	15 <	15 <	3 <	5 <	
NY	FM	2	84 269	84 356	231	I14-10	B	15 <	15 <	3 <	5 <	
NY	FM	2	84 269	84 356	231	I14-10	C	15 <	15 <	3 <	5 <	
NY	FM	2	84 269	84 356	231	I14-10	X	15 <	15 <	2	2	
NY	FM	2	84 269	84 356	231	I14-10	Y	16	15 <	2	2	
NY	FM	2	84 269	84 356	231	I14-10	Z	381	15 <	3	3	
NY	FM	2	84 269	84 356	250	I14-06	A	17	15 <	3	5 <	
NY	FM	2	84 269	84 356	250	I14-06	B	15 <	15 <	3 <	5 <	
NY	FM	2	84 269	84 356	250	I14-06	C	15 <	15 <	5	5 <	
NY	FM	2	84 269	84 356	244	H14-16	A	15	15 <	4	5	
NY	FM	2	84 269	84 356	244	H14-16	B	15 <	15 <	4	5 <	
NY	FM	2	84 269	84 356	244	H14-16	C	15 <	15 <	4	5 <	
NY	FM	3	84 356	85 79	231	L15-11	A	19	10 <	4	2 <	

NY	FM	3	84	356	85	79	231	L15-11	B	10 <	10 <	3	2 <	
NY	FM	3	84	356	85	79	231	L15-11	C	10 <	11	3	2 <	
NY	FM	3	84	356	85	79	244	L15-01	A	24	10 <	4	2 <	
NY	FM	3	84	356	85	79	244	L15-01	B	10 <	10 <	4	2 <	
NY	FM	3	84	356	85	79	244	L15-01	C	10 <	10 <	4	2 <	
NY	FM	3	84	356	85	79	250	K26-05	A	22	10 <	3 <	2 <	
NY	FM	3	84	356	85	79	250	K26-05	B	10 <	10 <	3	2 <	
NY	FM	3	84	356	85	79	250	K26-05	C	10 <	10 <	3	2 <	
NY	FM	3	84	356	85	79	250	K26-05	X	27	16	8	2 <	
NY	FM	3	84	356	85	79	250	K26-05	Y	32	16	8	2 <	
NY	FM	3	84	356	85	79	250	K26-05	Z	418	45	11	2 <	
NY	FM	4	85	79	85	172	231	K26-24	A	18	10 <	4	2 <	
NY	FM	4	85	79	85	172	231	K26-24	B	14	10 <	3 <	2 <	
NY	FM	4	85	79	85	172	231	K26-24	C	10 <	10 <	3 <	2 <	
NY	FM	4	85	79	85	172	244	K26-21	A	10 <	10 <	3 <	2 <	
NY	FM	4	85	79	85	172	244	K26-21	B	10 <	10 <	3 <	2 <	
NY	FM	4	85	79	85	172	244	K26-21	C	10 <	10 <	3 <	2 <	
NY	FM	4	85	79	85	172	244	K26-21	X	26	10 <	4	2 <	
NY	FM	4	85	79	85	172	244	K26-21	Y	30	10 <	6	2 <	
NY	FM	4	85	79	85	172	244	K26-21	Z	169	18	6	2 <	
NY	FM	4	85	79	85	172	250	L15-08	A	10 <	10 <	3	2 <	
NY	FM	4	85	79	85	172	250	L15-08	B	11	10 <	3	2 <	
NY	FM	4	85	79	85	172	250	L15-08	C	10	10 <	3 <	2 <	
NY	FM	A1	84	171	85	172	203	I11-09	A	9	9	3	2	
NY	FM	A1	84	171	85	172	203	I11-09	B	9 <	9 <	3	2	
NY	FM	A1	84	171	85	172	203	I11-09	C	9 <	9 <	4	2	
NY	FM	A1	84	171	85	172	203	I11-09	Z	1139	30	11	2	
NY	FM	A1	84	171	85	172	227	I36-14	A	9	9 <	4	3	
NY	FM	A1	84	171	85	172	227	I36-14	B	9 <	10	5	3	
NY	FM	A1	84	171	85	172	227	I36-14	C	9 <	9 <	6	3	
NY	FM	A1	84	171	85	172	227	I36-14	X	13	9 <	7	1	
NY	FM	A1	84	171	85	172	227	I36-14	Y	13	9 <	5	1	
NY	FM	A1	84	171	85	172	227	I36-14	Z	515	9 <	4	2	
NY	FM	A1	84	171	85	172	236	I14-16	A	11	9 <	3	3	
NY	FM	A1	84	171	85	172	236	I14-16	B	9 <	9 <	3	3	
NY	FM	A1	84	171	85	172	236	I14-16	C	9 <	9 <	3	2	
NY	FM	A2	85	172	86	177	N1	NA	A	20 <	15 <	5	5 <	AGG
NY	FM	A2	85	172	86	177	N2	NA	B	20 <	15 <	5	5 <	AGG
NY	FM	A2	85	172	86	177	N3	NA	C	20 <	15 <	10	5 <	AGG
NY	FM	A2	85	172	86	177	236	K26-13	X	20 <	15 <	5	5 <	
NY	FM	A2	85	172	86	177	236	K26-13	Y	20 <	15 <	5	5 <	
NY	FM	A2	85	172	86	177	236	K26-13	Z	90	15 <	5	5 <	
NY	FM	A4	87	176	88	190	203	K14-12	A	21	17 <	9	8 <	
NY	FM	A4	87	176	88	190	203	K14-12	Z	244	18	16	8 <	
NY	FM	A4	87	176	88	190	227	G34-08	A	20	17 <	8 <	8 <	
NY	FM	A4	87	176	88	190	227	G34-08	Z	716	17 <	10	8 <	
NY	FM	A4	87	176	88	190	236	G24-14	A	20	17 <	8 <	8 <	
NY	FM	A4	87	176	88	190	236	G24-14	Z	773	17	17	8 <	
NY	FM	B1	84	171	86	177	202	H36-19	A	20 <	15 <	5	5 <	ICP

NY	FM	B1	84 171	86 177	202 H36-19	B	20 <	15 <	5	5 <	
NY	FM	B1	84 171	86 177	202 H36-19	C	20 <	15 <	5 <	5 <	
NY	FM	B1	84 171	86 177	202 H36-19	Z	1342	20	10	2	
NY	FM	B1	84 171	86 177	239 I11-06	A	20	15 <	5	5 <	ICP
NY	FM	B1	84 171	86 177	239 I11-06	B	20 <	15 <	10	5 <	
NY	FM	B1	84 171	86 177	239 I11-06	C	20 <	15 <	5	5 <	
NY	FM	B1	84 171	86 177	259 L26-22	A	45	15 <	10	5 <	ICP
NY	FM	B1	84 171	86 177	259 L26-22	B	20 <	15 <	5	5 <	
NY	FM	B1	84 171	86 177	259 L26-22	C	20 <	15 <	5	5 <	
NY	FM	B1	84 171	86 177	259 L26-22	X	20 <	15 <	5	5 <	
NY	FM	B1	84 171	86 177	259 L26-22	Y	20	15 <	5	5 <	
NY	FM	B1	84 171	86 177	259 L26-22	Z	610	15 <	5	5 <	ICP
NY	FM	T1	84 171	87 176	228 I11-24	A	15	11	9	2 <	
NY	FM	T1	84 171	87 176	228 I11-24	Z	3736	23	5	4	
NY	FM	T1	84 171	87 176	238 M15-06	A	14	9	9	2 <	
NY	FM	T1	84 171	87 176	238 M15-06	Z	396	16	3	2 <	
NY	FM	T1	84 171	87 176	248 H36-14	A	18	10	7	2 <	
NY	FM	T1	84 171	87 176	248 H36-14	Z	1400	27	7	4	
NY	FM	Q1	84 171	88 190	224 H36-06	A	21	17 <	13	8 <	
NY	FM	Q1	84 171	88 190	224 H36-06	Z	3030	52	21	8	
NY	FM	Q1	84 171	88 190	205 M15-14	A	20	17 <	15	8 <	
NY	FM	Q1	84 171	88 190	205 M15-14	Z	3080	28	18	8 <	
NY	FM	Q1	84 171	88 190	208 L26-09	A	23	27	15	8 <	
NY	FM	Q1	84 171	88 190	208 L26-09	Z	1920	17 <	8 <	8 <	
DC	FM	1	84 224	84 320	231 I11-21	A	30	20	5	5 <	ICP
DC	FM	1	84 224	84 320	231 I11-21	B	15 <	20	5 <	5 <	ICP
DC	FM	1	84 224	84 320	231 I11-21	C	15 <	15 <	5 <	5 <	ICP
DC	FM	1	84 224	84 320	231 I11-21	X	30	30	11	2	
DC	FM	1	84 224	84 320	231 I11-21	Y	42	31	11	2	
DC	FM	1	84 224	84 320	231 I11-21	Z	450	100	24	5	
DC	FM	1	84 224	84 320	244 I36-22	A	30	15 <	5	5 <	ICP
DC	FM	1	84 224	84 320	244 I36-22	B	15 <	15 <	5 <	5 <	ICP
DC	FM	1	84 224	84 320	244 I36-22	C	15 <	15 <	5 <	5 <	ICP
DC	FM	1	84 224	84 320	250 I36-15	A	30	15 <	5	5 <	ICP
DC	FM	1	84 224	84 320	250 I36-15	B	15 <	15 <	5 <	5 <	ICP
DC	FM	1	84 224	84 320	250 I36-15	C	15 <	15 <	5 <	5 <	ICP
DC	FM	2	84 320	85 45	231 K26-15	A	26	15 <	7	5 <	
DC	FM	2	84 320	85 45	231 K26-15	B	15 <	15 <	4	5 <	
DC	FM	2	84 320	85 45	231 K26-15	C	15 <	15 <	3	5 <	
DC	FM	2	84 320	85 45	244 I14-09	A	35	26	18	5 <	
DC	FM	2	84 320	85 45	244 I14-09	B	15 <	15 <	6	5 <	
DC	FM	2	84 320	85 45	244 I14-09	C	15 <	15 <	6	5 <	
DC	FM	2	84 320	85 45	244 I14-09	X	42	17	9	4	
DC	FM	2	84 320	85 45	244 I14-09	Y	35	25	10	2	
DC	FM	2	84 320	85 45	244 I14-09	Z	999	86	41	6	
DC	FM	2	84 320	85 45	250 K26-07	A	26	15 <	8	5 <	
DC	FM	2	84 320	85 45	250 K26-07	B	15 <	15 <	4	5 <	
DC	FM	2	84 320	85 45	250 K26-07	C	15 <	15 <	11	5 <	

DC	FM	3	85	45	85	133	231	L15-10	A	21	10	4	2 <
DC	FM	3	85	45	85	133	231	L15-10	B	10	10 <	4	2 <
DC	FM	3	85	45	85	133	231	L15-10	C	10 <	10 <	3	2 <
DC	FM	3	85	45	85	133	244	K26-09	A	27	10 <	3	2 <
DC	FM	3	85	45	85	133	244	K26-09	B	10	10 <	3 <	2 <
DC	FM	3	85	45	85	133	244	K26-09	C	24	10 <	4	2 <
DC	FM	3	85	45	85	133	244	K26-09	X	33	18	6	2 <
DC	FM	3	85	45	85	133	244	K26-09	Y	38	21	7	2 <
DC	FM	3	85	45	85	133	244	K26-09	Z	358	69	11	4
DC	FM	3	85	45	85	133	250	L15-15	A	29	36	8	2 <
DC	FM	3	85	45	85	133	250	L15-15	B	11	11	4	2 <
DC	FM	3	85	45	85	133	250	L15-15	C	10	12	4	2 <
DC	FM	4	85	133	85	224	231	K26-22	A	47	16	4	2 <
DC	FM	4	85	133	85	224	231	K26-22	B	12	10 <	3	2 <
DC	FM	4	85	133	85	224	231	K26-22	C	10 <	10 <	4	2 <
DC	FM	4	85	133	85	224	244	L15-12	A	37	13	4	2 <
DC	FM	4	85	133	85	224	244	L15-12	B	16	10 <	3	2 <
DC	FM	4	85	133	85	224	244	L15-12	C	15	10 <	4	2 <
DC	FM	4	85	133	85	224	250	K26-16	A	40	13	5	2 <
DC	FM	4	85	133	85	224	250	K26-16	B	14	10 <	4	2 <
DC	FM	4	85	133	85	224	250	K26-16	C	17	10 <	3 <	2 <
DC	FM	4	85	133	85	224	250	K26-16	X	28	25	6	2 <
DC	FM	4	85	133	85	224	250	K26-16	Y	46	26	6	2 <
DC	FM	4	85	133	85	224	250	K26-16	Z	462	70	10	4
DC	FM	13	87	231	87	318	231	K14-17	A	36	10	14	9 <
DC	FM	13	87	231	87	318	231	K14-17	Z	420	37	10 <	11
DC	FM	13	87	231	87	318	244	K14-10	A	46	10 <	13	22
DC	FM	13	87	231	87	318	244	K14-10	Z	509	50	21	28
DC	FM	13	87	231	87	318	250	G24-09	A	42	10 <	18	9 <
DC	FM	13	87	231	87	318	250	G24-09	Z	351	32	10 <	9 <
DC	FM	14	87	318	88	48	244	G34-16	A	35	10 <	14	9 <
DC	FM	14	87	318	88	48	244	G34-16	Z	800	43	31	9 <
DC	FM	14	87	318	88	48	231	G34-04	A	39	10 <	10 <	9 <
DC	FM	14	87	318	88	48	231	G34-04	Z	910	76	32	9 <
DC	FM	14	87	318	88	48	250	K14-07	A	39	10	10 <	9 <
DC	FM	14	87	318	88	48	250	K14-07	Z	900	53	22	10
DC	FM	15	88	48	88	160	244	G22-20	A	57	76	15	10 <
DC	FM	15	88	48	88	160	244	G22-20	Z	668	138	18	10 <
DC	FM	15	88	48	88	160	250	G34-11	A	78	22	15 <	10 <
DC	FM	15	88	48	88	160	250	G34-11	Z	444	137	22	10 <
DC	FM	15	88	48	88	160	231	G34-14	A	73	35	15 <	10 <
DC	FM	15	88	48	88	160	231	G31-14	Z	634	149	16	10 <
DC	FM	16	88	180	88	258	231	J36-24	Z	768	168	28	7 <
DC	FM	16	88	180	88	258	244	J36-15	Z	533	131	25	7 <
DC	FM	16	88	180	88	258	250	J36-01	Z	684	159	32	7 <
DC	FM	A1	84	224	85	224	203	I11-14	A	33	12	4	3
DC	FM	A1	84	224	85	224	203	I11-14	B	11	9 <	3	2
DC	FM	A1	84	224	85	224	203	I11-14	C	10	9 <	3	2
DC	FM	A1	84	224	85	224	203	I11-14	Z	2218	52	14	18

DC	FM	A1	84	224	85	224	227	I36-18	A	33	13	4	2	
DC	FM	A1	84	224	85	224	227	I36-18	B	11	9 <	4	2	
DC	FM	A1	84	224	85	224	227	I36-18	C	11	9 <	4	2	
DC	FM	A1	84	224	85	224	227	I36-18	X	90	16	6	1	
DC	FM	A1	84	224	85	224	227	I36-18	Y	107	18	5	1	
DC	FM	A1	84	224	85	224	227	I36-18	Z	2045	50	8	14	
DC	FM	A1	84	224	85	224	236	I14-12	A	66	12	5	3	
DC	FM	A1	84	224	85	224	236	I14-12	B	12	17	4	3	
DC	FM	A1	84	224	85	224	236	I14-12	C	11	9 <	3	2	
DC	FM	A2	85	224	86	226	N1	NA	A	55	35	5	5 <	AGG
DC	FM	A2	85	224	86	226	N2	NA	B	25	35	5 <	5 <	AGG
DC	FM	A2	85	224	86	226	N3	NA	C	25	15 <	5 <	5 <	AGG
DC	FM	A2	85	224	86	226	236	I36-24	X	95	15 <	5	5 <	
DC	FM	A2	85	224	86	226	236	I36-24	Y	115	30	5 <	5 <	
DC	FM	A2	85	224	86	226	236	I36-24	Z	1545	75	10	10	
DC	FM	A4	87	223	88	258	203	G24-03	A	30	18	16	7 <	
DC	FM	A4	87	223	88	258	203	G24-03	Z	1280	65	17	24	
DC	FM	A4	87	223	88	258	227	K14-02	A	32	17 <	15	7 <	
DC	FM	A4	87	223	88	258	227	K14-02	Z	1540	69	20	25	
DC	FM	A4	87	223	88	258	236	G24-20	A	39	41	16	7 <	
DC	FM	A4	87	223	88	258	236	G24-20	Z	1520	101	22	25	
DC	FM	B1	84	224	86	226	202	H36-15	A	40	20	10	5 <	ICP
DC	FM	B1	84	224	86	226	202	H36-15	B	20 <	15 <	5 <	5 <	
DC	FM	B1	84	224	86	226	202	H36-15	C	20 <	15 <	5 <	5 <	
DC	FM	B1	84	224	86	226	202	H36-15	Z	4565	139	21	36	
DC	FM	B1	84	224	86	226	239	I11-10	A	40	20	5	5 <	ICP
DC	FM	B1	84	224	86	226	239	I11-10	B	20 <	15 <	5 <	5 <	
DC	FM	B1	84	224	86	226	239	I11-10	C	20 <	15 <	5 <	5 <	
DC	FM	B1	84	224	86	226	259	L26-23	A	40	15	5	5 <	ICP
DC	FM	B1	84	224	86	226	259	L26-23	B	20 <	15 <	5	5 <	
DC	FM	B1	84	224	86	226	259	L26-23	C	20 <	15 <	5	5 <	
DC	FM	B1	84	224	86	226	259	L26-23	X	200	20	10	5 <	
DC	FM	B1	84	224	86	226	259	L26-23	Y	315	30	10	5 <	
DC	FM	B1	84	224	86	226	259	L26-23	Z	4595	130	15	40	ICP
DC	FM	T1	84	224	87	223	228	I11-22	A	85	50	25	2 <	
DC	FM	T1	84	224	87	223	228	I11-22	X	225	30	15	2 <	
DC	FM	T1	84	224	87	223	228	I11-22	Y	245	35	15	2 <	
DC	FM	T1	84	224	87	223	228	I11-22	Z	5390	165	25	50	
DC	FM	T1	84	224	87	223	238	M15-07	A	70	45	15	2 <	
DC	FM	T1	84	224	87	223	238	M15-07	X	160	20	10	2 <	
DC	FM	T1	84	224	87	223	238	M15-07	Y	290	35	20	2 <	
DC	FM	T1	84	224	87	223	238	M15-07	Z	6515	180	30	55	
DC	FM	T1	84	224	87	223	248	H36-18	A	75	45	20	2 <	
DC	FM	T1	84	224	87	223	248	H36-18	X	235	25	10	2 <	
DC	FM	T1	84	224	87	223	248	H36-18	Y	320	30	20	2 <	
DC	FM	T1	84	224	87	223	248	H36-18	Z	5620	165	30	45	
DC	FM	Q1	84	224	88	258	224	H36-17	A	26	17 <	17	10	
DC	FM	Q1	84	224	88	258	224	H36-17	Z	10000	188	30	100	
DC	FM	Q1	84	224	88	258	205	M15-19	A	32	17	13	7 <	

DC	FM	Q1	84 224	88 258	205 M15-19	Z	7080	142	17	56
DC	FM	Q1	84 224	88 258	208 L26-04	A	37	20	17	7 <
DC	FM	Q1	84 224	88 258	208 L26-04	Z	6020	121	19	57
CH	FM	9	86 198	86 293	231 K14-13	A	120	12	4 <	2 <
CH	FM	9	86 198	86 293	231 K14-13	Z	1621	32	9	8
CH	FM	9	86 198	86 293	244 K13-22	A	99	12	5	2 <
CH	FM	9	86 198	86 293	244 K13-22	Z	1133	30	9	6
CH	FM	9	86 198	86 293	250 G22-04	A	133	10	8	2 <
CH	FM	9	86 198	86 293	250 G22-04	Z	1400	30	19	6
CH	FM	10	86 293	87 33	231 G22-21	A	35	14	5	2 <
CH	FM	10	86 293	87 33	231 G22-21	Z	2284	41	15	6
CH	FM	10	86 293	87 33	244 G22-06	A	51	20	24	6
CH	FM	10	86 293	87 33	244 G22-06	Z	2067	33	13	6
CH	FM	10	86 293	87 33	250 K13-02	A	47	27	16	2 <
CH	FM	10	86 293	87 33	250 K13-02	Z	2149	36	18	6
CH	FM	11	87 33	87 111	231 K13-06	A	70	12	6	3
CH	FM	11	87 33	87 111	231 K13-06	Z	1122	38	13	9
CH	FM	11	87 33	87 111	250 G22-05	A	87	15	5	2 <
CH	FM	11	87 33	87 111	250 G22-05	Z	1090	31	9	8
CH	FM	12	87 111	87 209	231 K13-11	A	260	15	10	2
CH	FM	12	87 111	87 209	231 K13-11	Z	1450	40	20	10
CH	FM	12	87 111	87 209	244 G22-10	A	215	15	20	2 <
CH	FM	12	87 111	87 209	244 G22-10	Z	1245	40	10	10
CH	FM	12	87 111	87 209	250 K13-04	A	150	15	15	2 <
CH	FM	12	87 111	87 209	250 K13-04	Z	1570	40	15	10
CH	FM	A3	86 198	87 209	203 K13-16	A	215	15	15	2 <
CH	FM	A3	86 198	87 209	203 K13-16	B	30	15	15	2 <
CH	FM	A3	86 198	87 209	203 K13-16	C	25	15	10	2 <
CH	FM	A3	86 198	87 209	203 K13-16	X	130	20	10	2 <
CH	FM	A3	86 198	87 209	203 K13-16	Y	185	20	15	2 <
CH	FM	A3	86 198	87 209	203 K13-16	Z	2840	45	15	25
CH	FM	A3	86 198	87 209	227 G34-18	A	250	15	20	2 <
CH	FM	A3	86 198	87 209	227 G34-18	X	85	20	20	2 <
CH	FM	A3	86 198	87 209	227 G34-18	Y	150	20	15	2 <
CH	FM	A3	86 198	87 209	227 G34-18	Z	3455	55	10	35
CH	FM	A3	86 198	87 209	236 K14-16	A	210	15	25	2
CH	FM	A3	86 198	87 209	236 K14-16	X	85	20	20	2 <
CH	FM	A3	86 198	87 209	236 K14-16	Y	115	20	20	2 <
CH	FM	A3	86 198	87 209	236 K14-16	Z	2615	50	15	30
CH	FM	A4	87 209	88 223	203 G24-12	A	65	24	13	7 <
CH	FM	A4	87 209	88 223	203 G24-12	Z	2620	44	11	22
CH	FM	A4	87 209	88 223	227 K14-05	A	81	17 <	9	7 <
CH	FM	A4	87 209	88 223	227 K14-05	Z	3140	29	12	28
CH	FM	A4	87 209	88 223	236 G24-08	A	75	17 <	13	7 <
CH	FM	A4	87 209	88 223	236 G24-08	Z	2230	34	14	21
CH	FM	B2	86 198	88 223	239 K14-23	A	1100	21	14	7 <
CH	FM	B2	86 198	88 223	239 K14-23	Z	4710	44	17	46
CH	FM	B2	86 198	88 223	202 G34-10	A	88	17 <	13	7 <

CH	FM	B2	86	198	88	223	202 G34-10	Z	5570	36	15	49
CH	FM	B2	86	198	88	223	259 G22-14	A	89	17 <	14	7 <
CH	FM	B2	86	198	88	223	259 G22-14	Z	4210	50	14	42
OHM DFM		A4	87	209	88	223	359 G24-07	A	890	67	28	10
OHM DFM		A4	87	209	88	223	359 G24-07	Z	2610	70	27	20
OHM DFM		A4	87	209	88	223	384 G34-17	A	725	43	20	9
OHM DFM		A4	87	209	88	223	384 G34-17	Z	3440	70	28	23
OHM SFM		A4	87	209	88	223	315 G24-15	A	558	68	26	9
OHM SFM		A4	87	209	88	223	315 G24-15	Z	2980	76	21	27
OHM SFM		A4	87	209	88	223	329 G34-07	A	257	66	36	9
OHM SFM		A4	87	209	88	223	329 G34-07	Z	2460	44	14	23

Documentation for Briquette Surface Chemistry Files

Cation files (Mg, Al, Cd, Mn, Ba, Be, Ni, Pb, Co, Cr, Cu, Fe, Sr, V, Zn)

Separate files for limestone and marble

COLUMN HEADINGS:

SITE = Field Site; MAT = Material Type; PER = Exposure Period;
 SYR = Start Year (of exposure); SJD = Start Julian Date; EYR = End Year; EJD = End Julian Date;
 SLOT = Briquette Slot Location; SAMPLE = Briquette Sample Number; LAY = Layer Designation;

Flags ("<") for results below detection limit are found in adjacent column to the right; column heading is appropriate cation symbol preceded by the letter "D" (i.e. entry of flag in the "DMg" column indicates that the analytic result for magnesium was below the detection limit)

KEY TO SPECIFIC ENTRIES:

SITES -----

CB=Characterization
 NC=North Carolina
 NJ=New Jersey
 NY=New York
 DC=Washington DC
 OH=Ohio
 OHM=Ohio Moveable Shelter
 (Sprayed and Dry regimes)

MATERIAL TYPES -----

FL=Fresh Limestone	WL=Weathered Limestone
FM=Fresh Marble	WM=Weathered Marble
SFL=Sprayed regime FL	SWL=Sprayed regime WL
SFM=Sprayed regime FM	SWM=Sprayed regime WM
DFL=Dry Regime FL	DWL=Dry regime WL
DFM=Dry regime FM	DWM=Dry regime WM

TIME PERIODS -----

Quarters = 1, 2, 3, 4, 5, etc. (starting from Summer 1984)
 Annuals = A1, A2, A3, etc. (Ax, where x is 1-5th year)
 Biennials = B1, B2, etc. (Bx, where x is 1-3rd biennial cycle)
 Triennial = T1, T2 (1st and 2nd triennial cycles)
 Quadrennial = Q1 (1st quadrennial cycle)
 Quinquennial = C1

LAYERS-----

A,B,C=Top 3 layers
 (A=outermost top layer)
 U,V,W,X,Y,Z=Bottom layers
 (Z=outermost bottom layer)

COMMENTS-----

AGG=Analysis of aggregated sample
 BULK=Analysis of volumetric center of briquette

MISC.-----

< = flag for result below detection limit
 ? = analytical result questioned by chem lab
 NA, N1, N2, and N3 = not applicable

NJ	RL	1	84 157	84 251	144 GU1-15	B 2760	27	1 <	57	10	0.5 <	5 <	10 <	5 <	5 <	4	210	210	5 <	8	AGG
NJ	RL	1	84 157	84 251	144 GU1-15	C 2710	25	1 <	55	8	0.5 <	5 <	10 <	5 <	5	3	190	220	5 <	8	
NJ	RL	B1	84 157	86 169	159 GL2-17	A 2670	8F	1 ?	66	5 <	0.5 <	5 <	10 ?	5 <	5 <	2	600	220	10 <	25	
NJ	RL	B1	84 157	86 169	102 IU5-07	A 2570	87	1 ?	70	5 <	0.5 <	5 <	10 <	5 <	5 <	3	320	210	10 <	27	
NJ	RL	B1	84 157	86 169	139 HL4-09	A 2620	88	1 <	63	5 <	0.5 <	5 <	10 <	5 <	5 <	2	350	210	10 <	27	
NJ	RL	B1	84 157	86 169	N1 NA	B 2600	49	1 <	61	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	370	210	10 <	14	AGG
NJ	RL	B1	84 157	86 169	N1 NA	C 2600	53	1 <	58	5 <	0.5 <	5 <	10 <	5 <	5 <	2	370	220	10 <	11	AGG
NJ	RL	B1	84 157	86 169	139 HL4-09	X 2620	30	1 <	63	5 <	0.5 <	5 <	10 <	5 <	5 <	2	310	230	10 <	8	
NJ	RL	B1	84 157	86 169	139 HL4-09	Y 2640	31	1 <	65	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	320	230	10 <	8	
NJ	RL	B1	84 157	86 169	139 HL4-09	Z 2480	20 <	1 <	62	5	0.5 <	5 <	10 <	5 <	5 <	3	370	220	10 <	10	
NY	RL	1	84 171	84 269	131 HU4-14	A 2710	25	1 <	64	5 <	0.5 <	5 <	10 <	5 <	5 <	5	220	200	5 <	10	
NY	RL	1	84 171	84 269	131 HU4-14	B 2740	20	1 <	63	14	0.5 <	5 <	10 <	5 <	5 <	8	220	180	5 <	10	
NY	RL	1	84 171	84 269	131 HU4-14	C 2720	20	1 <	62	15	0.5 <	5 <	10 <	5 <	5 <	6	200	200	5 <	7	
NY	RL	1	84 171	84 269	150 IU2-09	A 2770	20	1 <	75	8	0.5 <	5 <	10 <	5 <	5 <	7	250	200	5 <	10	
NY	RL	1	84 171	84 269	150 IU2-09	B 2670	22	1 <	63	10	0.5 <	5 <	10 <	5 <	5 <	3	240	210	5 <	8	
NY	RL	1	84 171	84 269	150 IU2-09	C 2690	22	1 <	60	5 <	0.5 <	5 <	10 <	5 <	5 <	4	250	200	5 <	7	
NY	RL	1	84 171	84 269	144 GU1-14	A 2780	30	1 <	57	5 <	0.5 <	5 <	10 <	5 <	5 <	4	210	220	5 <	9	
NY	RL	1	84 171	84 269	144 GU1-14	B 2800	27	1 <	56	5 <	0.5 <	5 <	10 <	5 <	5 <	8	200	220	5 <	10	
NY	RL	1	84 171	84 269	144 GU1-14	C 2880	33	1 <	56	5 <	0.5 <	5 <	10 <	5 <	5 <	9	220	210	5 <	10	
NY	RL	B1	84 171	86 177	159 GL2-05	A 2670	51	1 <	65	5 <	0.5 <	5 <	10 <	5 <	5 <	2	300	220	10 <	13	
NY	RL	B1	84 171	86 177	102 IU5-11	A 2600	59	1 <	71	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	380	220	10 <	11	
NY	RL	B1	84 171	86 177	139 HL4-19	A 2660	96	1 <	65	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	380	220	10 <	15	
NY	RL	B1	84 171	86 177	N1 NA	B 2660	48	1 <	61	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	340	230	10 <	8	AGG
NY	RL	B1	84 171	86 177	N1 NA	C 2670	42	1 <	60	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	330	220	10 <	8	AGG
NY	RL	B1	84 171	86 177	139 HL4-19	X 2420	20 <	1 <	64	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	280	210	10 <	5	
NY	RL	B1	84 171	86 177	139 HL4-19	Y 2440	20 <	1 <	65	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	280	220	10 <	6	
NY	RL	B1	84 171	86 177	139 HL4-19	Z 2490	40	1 <	69	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	280	230	10 <	6	
DC	RL	1	84 224	84 320	144 GU1-11	A 2720	42	1 <	62	5 <	0.5 <	5 <	10 <	5 <	6	10	220	220	5 <	14	
DC	RL	1	84 224	84 320	144 GU1-11	B 2670	28	1 <	58	5 <	0.5 <	5 <	10 <	5 <	5	11	200	220	5 <	10	
DC	RL	1	84 224	84 320	144 GU1-11	C 2720	32	1 <	58	5 <	0.5 <	5 <	10 <	5 <	6	9	190	220	5 <	9	
DC	RL	1	84 224	84 320	150 HU4-04	A 2570	46	1 <	67	5 <	0.5 <	5 <	10 <	5 <	5	5	270	210	5 <	13	
DC	RL	1	84 224	84 320	150 HU4-04	B 2610	35	1 <	62	5 <	0.5 <	5 <	10 <	5 <	5	6	230	210	5 <	10	
DC	RL	1	84 224	84 320	150 HU4-04	C 2580	25	1 <	58	5 <	0.5 <	5 <	10 <	5 <	5	5	230	210	5 <	8	
DC	RL	1	84 224	84 320	131 HU4-18	A 2650	42	1 <	64	5 <	0.5 <	5 <	10 <	5 <	5	6	250	220	5 <	12	
DC	RL	1	84 224	84 320	131 HU4-18	B 2610	34	1 <	61	5 <	0.5 <	5 <	10 <	5 <	5	5	230	220	5 <	9	
DC	RL	1	84 224	84 320	131 HU4-18	C 2670	26	1 <	60	5 <	0.5 <	5 <	10 <	5 <	6	5	220	220	5 <	8	
DC	RL	1	84 224	84 320	131 HU4-18	X 2690	58	1 <	56	5 <	0.5 <	5 <	10 <	5 <	5	5	220	220	5 <	8	
DC	RL	1	84 224	84 320	131 HU4-18	Y 2670	25	1 <	58	5 <	0.5 <	5 <	10 <	5 <	5	4	220	220	5 <	8	
DC	RL	1	84 224	84 320	131 HU4-18	Z 2710	30	1 <	60	5 <	0.5 <	5 <	10 <	5 <	6	6	230	230	5 <	9	
DC	RL	B1	84 224	86 226	159 GL2-06	A 2610	100	1 <	61	5 <	0.5 <	5 <	10 <	5 <	5	3	400	210	10 <	21	
DC	RL	B1	84 224	86 226	102 IU5-15	A 2550	90	1 <	63	5 <	0.5 <	5 <	10 <	5 <	5	3	350	210	10 <	21	
DC	RL	B1	84 224	86 226	139 HL4-10	A 2640	94	1 <	60	5 <	0.5 <	5 <	10 <	5 <	5	3	370	210	10 <	21	
DC	RL	B1	84 224	86 226	N1 NA	B 2580	39	1 <	58	5 <	0.5 <	5 <	10 <	5 <	5	3	300	220	10 <	12	AGG
DC	RL	B1	84 224	86 226	N1 NA	C 2500	27	1 <	55	5 <	0.5 <	5 <	10 <	5 <	5	2	270	210	10 <	8	AGG
DC	RL	B1	84 224	86 226	139 HL4-10	X 2460	20 <	1 <	59	5 <	0.5 <	5 <	10 <	5 <	5	2 <	300	200	10 <	7	
DC	RL	B1	84 224	86 226	139 HL4-10	Y 2490	26	1 <	59	5 <	0.5 <	5 <	10 <	5 <	5	2 <	330	210	10 <	7	
DC	RL	B1	84 224	86 226	139 HL4-10	Z 2440	31	1 <	57	6	0.5 <	5 <	10 <	5 <	5	3	410	230	10 <	10	

ANL's ICP ANALYSES / MARBLE

SITE	MAT	PER	SYR	SJD	EVR	EJD	SLOT	SAMPLE	LAY	Mg	DAI	Cd	Co	Mn	DMn	Ba	DBa	Be	DBe	Ni	DNI	Pb	DPb	Co	DCo	Cr	DCr	Cu	DCu	Fe	DFe	Sr	DSr	V	DV	Zn	DZn	COMMENT
CB	FM	NA	NA	NA	NA	NA	NA	N1	N15-20	A	1670	32	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	9	340	170	5	3						
CB	FM	NA	NA	NA	NA	NA	NA	N1	N15-20	B	1640	26	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	8	310	160	5	3							
CB	FM	NA	NA	NA	NA	NA	NA	N1	N15-20	C	1630	26	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	8	300	160	5	2							
CB	FM	NA	NA	NA	NA	NA	NA	N1	I11-13	A	1320	24	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	8	310	150	5	3							
CB	FM	NA	NA	NA	NA	NA	NA	N1	I11-13	B	1340	23	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	8	310	150	5	2							
CB	FM	NA	NA	NA	NA	NA	NA	N1	I11-13	C	1330	27	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	8	320	150	5	3							
CB	FM	NA	NA	NA	NA	NA	NA	N1	H36-12	A	2550	110	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	250	160	5	2						
CB	FM	NA	NA	NA	NA	NA	NA	N1	H36-12	B	2520	88	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	250	160	5	2						
CB	FM	NA	NA	NA	NA	NA	NA	N1	H36-12	C	2330	62	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	4	250	160	5	2							
NC	FM	1	84	146	84	237	231	N15-01	A	1420	20	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	270	170	5	2						
NC	FM	1	84	146	84	237	231	N15-01	B	1400	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	4	260	170	5	2							
NC	FM	1	84	146	84	237	231	N15-01	C	1410	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	260	170	5	2						
NC	FM	1	84	146	84	237	250	C16-11	A	1590	20	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	8	290	160	5	3							
NC	FM	1	84	146	84	237	250	C16-11	B	1540	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	4	280	160	5	2							
NC	FM	1	84	146	84	237	250	C16-11	C	1540	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	270	160	5	2						
NC	FM	1	84	146	84	237	244	K36-17	A	1530	24	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	9	390	140	5	4							
NC	FM	1	84	146	84	237	244	K36-17	B	1570	26	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	320	140	5	2							
NC	FM	1	84	146	84	237	244	K36-17	C	1560	27	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	280	130	5	2						
NC	FM	A1	84	146	85	136	203	I36-17	A	2300	95	1	1	21	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	490	160	5	2						
NC	FM	A1	84	146	85	136	203	I36-17	B	2290	110	1	1	21	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	590	160	5	2						
NC	FM	A1	84	146	85	136	203	I36-17	C	2290	110	1	1	21	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	610	160	5	2						
NC	FM	A1	84	146	85	136	227	K36-06	A	1910	79	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	220	180	5	2						
NC	FM	A1	84	146	85	136	227	K36-06	B	1910	70	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	210	180	5	2						
NC	FM	A1	84	146	85	136	227	K36-06	C	1870	54	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	210	180	5	2						
NC	FM	A1	84	146	85	136	236	E26-12	A	2070	26	1	1	18	5	5	0.5	5	5	10	10	5	5	5	5	5	5	220	220	5	3							
NC	FM	A1	84	146	85	136	236	E26-12	B	2080	23	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	230	230	5	3							
NC	FM	A1	84	146	85	136	236	E26-12	C	2070	15	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	5	240	220	5	2							
NC	FM	A1	84	146	85	136	203	I36-17	X	2960	192	1	1	21	5	5	0.5	5	5	10	10	5	5	5	5	5	5	480	180	5	2							
NC	FM	A1	84	146	85	136	203	I36-17	Y	2790	152	1	1	20	5	5	0.5	5	5	10	10	5	5	5	5	5	5	460	150	5	2							
NC	FM	A1	84	146	85	136	203	I36-17	Z	2850	164	1	1	20	5	5	0.5	5	5	10	10	5	5	5	5	5	5	440	180	5	2							
NC	FM	B1	84	146	86	155	239	I36-07	A	1340	20	1	1	16	5	5	0.5	5	5	10	10	5	5	5	5	5	2	290	139	10	2							
NC	FM	B1	84	146	86	155	202	K36-01	A	1660	20	1	1	16	5	5	0.5	5	5	10	10	5	5	5	5	5	2	210	140	10	2							
NC	FM	B1	84	146	86	155	259	E26-01	A	1610	20	1	1	16	5	5	0.5	5	5	10	10	5	5	5	5	5	2	230	174	10	2							
NC	FM	B1	84	146	86	155	259	E26-01	Z	2320	98	1	1	16	5	5	0.5	5	5	10	10	5	5	5	5	5	2	250	182	10	2							
NJ	FM	1	84	157	84	251	231	I11-01	A	1380	20	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	290	140	5	2						
NJ	FM	1	84	157	84	251	231	I11-01	B	1380	20	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	4	290	140	5	2							
NJ	FM	1	84	157	84	251	231	I11-01	C	1390	33	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	290	140	5	2						
NJ	FM	1	84	157	84	251	250	G26-21	A	3110	140	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	300	170	5	3						
NJ	FM	1	84	157	84	251	250	G26-21	B	3220	150	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	290	170	5	2						
NJ	FM	1	84	157	84	251	250	G26-21	C	3130	140	1	1	19	5	5	0.5	5	5	10	10	5	5	5	5	5	5	5	300	170	5	2						
NJ	FM	1	84	157	84	251	244	G36-12	A	1740	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	10	270	170	5	5							
NJ	FM	1	84	157	84	251	244	G36-12	B	1770	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	10	270	170	5	3							
NJ	FM	1	84	157	84	251	244	G36-12	C	1760	20	1	1	17	5	5	0.5	5	5	10	10	5	5	5	5	5	10											

NJ	FM	B1	84 157	86 169	259 H36-08	A 2370	52	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	230	151	10 <	2
NJ	FM	B1	84 157	86 169	259 H36-08	Z 1690	20 <	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	270	153	10 <	2
NY	FM	1	84 171	84 269	231 I11-05	A 1410	25	1 <	19	5 <	0.5 <	5 <	10 <	5 <	5 <	10	300	150	5 <	4
NY	FM	1	84 171	84 269	231 I11-05	B 1360	24	1 <	19	5 <	0.5 <	5 <	10 <	5 <	5 <	9	300	150	5 <	4
NY	FM	1	84 171	84 269	231 I11-05	C 1390	23	1 <	19	5 <	0.5 <	5 <	10 <	5 <	5 <	10	300	150	5 <	4
NY	FM	1	84 171	84 269	250 I36-08	A 1750	25	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	6	230	180	5 <	3
NY	FM	1	84 171	84 269	250 I36-08	B 1810	28	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	7	230	180	5 <	2 <
NY	FM	1	84 171	84 269	250 I36-08	C 1780	24	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	6	220	180	5 <	2 <
NY	FM	1	84 171	84 269	244 G36-13	A 1930	30	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	6	290	180	5 <	3
NY	FM	1	84 171	84 269	244 G36-13	B 1920	33	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	6	290	180	5 <	2 <
NY	FM	1	84 171	84 269	244 G36-13	C 1990	34	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	6	290	180	5 <	2 <
NY	FM	B1	84 171	86 177	239 I11-06	A 1300	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	270	141	10 <	2 <
NY	FM	B1	84 171	86 177	202 H36-19	A 1750	20 <	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	310	161	10 <	2 <
NY	FM	B1	84 171	86 177	259 L26-22	A 2040	20 <	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	320	184	10 <	3
NY	FM	B1	84 171	86 177	259 L26-22	Z 1240	20 <	1 <	15	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	230	160	10 <	2 <
DC	FM	1	84 224	84 320	231 I11-21	A 1590	20 <	1 <	18	5 <	0.5 <	5 <	10 <	5 <	5 <	9	310	180	5 <	3
DC	FM	1	84 224	84 320	231 I11-21	B 1580	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	8	300	180	5 <	2
DC	FM	1	84 224	84 320	231 I11-21	C 1590	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	7	300	180	5 <	2
DC	FM	1	84 224	84 320	250 I36-15	A 1400	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	4	230	150	5 <	2 <
DC	FM	1	84 224	84 320	250 I36-15	B 1400	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	4	230	150	5 <	2 <
DC	FM	1	84 224	84 320	250 I36-15	C 1390	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	3	230	150	5 <	2 <
DC	FM	1	84 224	84 320	244 I36-22	A 1500	20 <	1 <	18	5 <	0.5 <	5 <	10 <	5 <	5 <	4	280	160	5 <	2 <
DC	FM	1	84 224	84 320	244 I36-22	B 1480	20 <	1 <	18	5 <	0.5 <	5 <	10 <	5 <	5 <	4	280	160	5 <	2 <
DC	FM	1	84 224	84 320	244 I36-22	C 1500	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	3	280	160	5 <	2 <
DC	FM	B1	84 224	86 226	239 I11-10	A 1160	20 <	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	2	250	133	10 <	3
DC	FM	B1	84 224	86 226	202 H36-15	A 1560	33	1 <	16	5 <	0.5 <	5 <	10 <	5 <	5 <	2 <	300	160	10 <	2
DC	FM	B1	34 224	86 226	259 L26-23	A 1800	26	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	7	250	142	10 <	6
DC	FM	B1	84 224	86 226	259 L26-23	Z 3550	90	1 <	17	5 <	0.5 <	5 <	10 <	5 <	5 <	2	290	163	10 <	2

Distribution for ANL-89/34Internal:

R. Dalton
 H. Drucker
 N. Heeg
 P. Hess
 E. Huff
 K. Jensen
 D. Kupperman
 C. A. Malefyt (2)

A. C. Raptis
 K. J. Reimann (7)
 D. Schmalzer
 J. Shannon
 D. Streets
 C. Till
 R. A. Valentin
 R. W. Weeks

M. Wesely
 J. Wozniak
 ANL Patent Dept.
 ANL Contract File
 TIS (3)

External:

DOE/OSTI (2)
 ANL Libraries
 DOE CH

D. T. Goldman
 F. Herbaty

Materials and Components Technology Division Review Committee:

H. Berger, Industrial Quality, Inc., Gaithersburg, MD
 M. S. Dresselhaus, Massachusetts Institute of Technology, Cambridge, MA
 S. J. Green, Electric Power Research Institute, Palo Alto, CA
 R. A. Greenkorn, Purdue U., West Lafayette, IN
 C.-Y. Li, Cornell University, Ithaca, NY
 P. G. Shewmon, Ohio State University, Columbus
 R. E. Smith, Electric Power Research Institute, Charlotte, NC

National Park Service:

L. Nelson
 J. Rogers
 S. Sherwood (20)

U.S. Geological Survey:

P. Baedeker
 M. Kingston
 J. Morgan
 V. Mossotti
 R. Pickering
 M. Reddy
 E. Spiker

Colorado School of Mines:

D. Langmuir

END

**DATE
FILMED**

01 / 27 / 92