Progress Report

Covering

ANL's Electric Vehicle Battery Activities

for

USABC

for the period

April - September 1992

Prepared for the

U.S. Advanced Battery Consortium

ANL/CMT/RP--78324

TABLE OF CONTENTS

	Page
Section I PROJECT HIGHLIGHTS	1
Section II INTRODUCTION	2
Section III TECHNICAL PROGRESS AND STATUS	3
TASK AREA 1.0 LITHIUM/SULFIDE BATTERIES	3
1.1 Bipolar Battery R&D	3
1.2 Li/FeS ₂ Project Planning	5
TASK AREA 2.0 NICKEL/METAL HYDRIDE SUPPORT	6
2.1 OBC Program Support	6
2.2 Nickel Electrode Technology Support	7
TASK AREA 3.0 EV BATTERY PERFORMANCE AND LIFE EVALUATION	9
3.1 Performance and Life Tests	9
3.2 Post-Test Analyses	9
3.3 Battery Test Procedure Tiger Team Support	10

Section I

PROJECT HIGHLIGHTS

TASK AREA 1.0: LITHIUM/SULFIDE BATTERIES

- Preliminary results of an evaluation on a new type of rigid composite separator in a 3-cm diameter cell were encouraging. This type of dimensionally-stable separator could help extend the life of bipolar lithium/iron sulfide cells.
- Two 4-cell 13-cm diameter Li-Al/FeS₂ stacks were fabricated to refine assembly processes for stacks employing all molybdenum hardware. A post-weld Hastalloy B brazing operation was developed to fill voids in the peripheral weld and produce leak-free moly-ring/moly-ring joints. This process was implemented in the assembly of the second stack.
- ANL continued to work with the USABC to develop detailed SOWs and negotiate the terms and conditions of Cooperative Research and Development Agreements for work to be performed at ANL.

TASK AREA 2.0: NICKEL/METAL HYDRIDE SUPPORT

- ANL participated in a design review of the Ni/MH cells that Ovonic Battery Company (OBC) will develop as their baseline EV cell. This cell will have a rated capacity in the range of 35-40 Ah.
- In July, ANL participated in a visit to Inco's Toronto research center, as part of a TAC delegation. Inco discussed advances in materials processing that hold promise for lower-cost nickel electrodes that employ Ni(OH)₂ paste and reticulated nickel substrates. The new reticulated substrates exhibit >97% porosity.

TASK AREA 3.0: EV BATTERY PERFORMANCE AND LIFE EVALUATION

- ANL/ADL continued to evaluate Ni/MH cells produced by OBC. A 30 Ah cell achieved a life of 505 cycles (the longest life to date in tests at ANL for this technology). Also, higher capacity (35-Ah rated capacity) cells have been received and placed on test.
- ANL developed detailed step-by-step procedures for conducting post-test analysis of Ni/MH cells and used these procedures to establish a set of general steps to be followed in the examination of any battery technology. This is the first step in developing standardized procedures for post-test analysis.

Section II

INTRODUCTION

The Electrochemical Technology Program at Argonne National Laboratory (ANL) provides advanced battery R&D; technology transfer to industry; technical analyses, assessments, modeling, and databases; and independent testing and post-test analyses of advanced batteries. These capabilities and services are being offered to the US Advanced Battery Consortium (USABC) and Cooperative Research and Development Agreements (CRADAs) are being negotiated for USABC-sponsored work at ANL. A small portion of DOE's cost share for USABC projects has been provided to ANL to continue R&D and testing activities on key technologies that were previously supported directly by DOE.

This report summarizes progress on these USABC projects during the period of April 1 through September 30, 1992. In this report, the objective, background, technical progress, and status are described for each task. The work is organized into the following task areas:

- 1.0 Lithium/Sulfide Batteries
- 2.0 Nickel/Metal Hydride Support
- 3.0 EV Battery Performance and Life Evaluation

Section III of this report recounts the work performed during this reporting period on each task within these three task areas.

Section III

TECHNICAL PROGRESS AND STATUS

TASK AREA 1.0 LITHIUM/SULFIDE BATTERIES

This task area encompasses research and development of the Li/FeS₂ battery technology for electric and hybrid vehicle applications. The Li/FeS₂ system is an advanced technology with projected performance capabilities that are about double those of the Li/FeS technology. This technology offers a high degree of performance/design flexibility for a wide variety of electric and hybrid vehicle applications. It is in the cell and stack development stage and has exhibited 200 Wh/kg, 400 W/kg, and >500 cycles in electrolyte-starved bipolar cells.

This task area is organized into two tasks:

Task 1.1 Bipolar Battery R&D

Task 1.2 Li/FeS₂ Project Planning

1.1 Bipolar Battery R&D

Objective and Background

ANL has been conducting a low-level R&D project to develop high-performance bipolar LiAl/FeS₂ batteries for electric vehicle applications. Present efforts are directed at scaling up 3-cm diameter laboratory cells to 13-cm diameter EV cells and stacks. During FY1991, 13-cm diameter bipolar LiAl/FeS₂ cells were built and tested. The first LiAl/FeS₂ cells demonstrated 180 Wh/kg at the 30 W/kg discharge rate and the ability to provide >400 W/kg peak specific power.

The main objective of this task is to develop a bipolar LiAl/FeS₂ battery with acceptable performance and life characteristics for use in a variety of electric vehicle applications. Key areas of R&D involve the refinement of ANL's chalcogenide-based peripheral seal for 13-cm diameter cells and stacks, development of low-cost bipolar plates, and refinement of the 13-cm diameter bipolar cell/stack design and fabrication processes.

Technical Progress and Status

ANL continued to work on the development of 13-cm diameter bipolar lithium/iron disulfide cells and initiated efforts on the establishment of a data base for this cell and stack technology. In the area of baseline cell and stack development, efforts were directed at (1) refining the metal-to-ceramic peripheral seal, (2) developing improved separator systems, and (3) building and testing baseline 13-cm diameter bipolar cells and 4-cell stacks.

An internal review of the planned peripheral seal development steps and associated seal design evolutions was conducted in early April. The objective of the seal development effort is to simultaneously improve seal durability and enhance assembly. The designs consider several potential bipolar plate materials. The design evolution steps were judged to be a logical progression and they are currently being pursued.

The proper sizing of components is critical to routinely achieving a successful seal. Undersized Al_2O_3 fixture rings caused low yields, until a new batch of properly sized rings were received. Refined seal processing steps are being developed, which produce seals that exhibit acceptably high (>20 mega ohm) resistances. To date, more than two dozen 13-cm ID bipolar seals, of the ring/ring design, have been fabricated. Two four-cell bipolar Li/FeS_2 stacks were assembled using molybdenum ring/molybdenum ring seals. Our plan is to replace this type of Mo ring/Mo ring seal with a steel ring/Mo cup/steel ring seal, which will allow final stack assembly and integration to be accomplished with a steel-to-steel weld, rather than a Mo-to-Mo weld. Seals of this type have been successfully fabricated, but not yet assembled into stacks.

Efforts are being conducted to develop alternative ceramic sealants that can be fired at lower temperatures than our current sealants. A new chalcogenide composition, that fuses at a temperature 150°C below our current chalcogenide composition, is exhibiting promise in preliminary evaluations. It appears to possess a comparable bond strength and is currently being evaluated in 3-cm diameter bipolar cell seal.

Also, methods of evaluating the mechanical properties and the leak-proof integrity of the seals are being developed. A 4-point fracture test for metal-to-ceramic bonded samples is being used to establish relative fracture strengths and a leak test apparatus for 13-cm diameter seals has been set up and is being used to leak check seals.

Efforts on developing improved separators are investigating use of thinner $\text{MgO}/\text{electrolyte}$ pressed pellets, as well as a new rigid separator system. Also, SAFT produced a new die, based on ANL's sizing requirements, that produces properly-sized (larger diameter) $\text{MgO}/\text{electrolyte}$ pressed pellets for use with ANL's cell components. The new die was used to press 1.2, 1.8, and 2.7 mm thick $\text{MgO}/\text{electrolyte}$ pellets. The 1.8 mm thick pellets are the standard thickness.

In the development of a rigid separator system, promising results were obtained with a composite structure that utilizes MgO (Maglite S) and chalcogenide pressed powders between perforated metal sheets. This sandwich configuration is fired to form a rigid bonded composite with $\sim 65\%$ open porosity. The open pores are filled with electrolyte in a post-firing vacuum infiltration step. A 3-cm diameter pellet cell, incorporating this type of separator, was built and tested for 50 cycles and 550 hours. A post-test metallographic examination of the cell indicated that this separator system was effective in preventing migration of electrode active materials into the separator, was wetted well by the electrolyte, and exhibited good chemical and mechanical stability.

Several 13-cm diameter bipolar LiAl/FeS_2 cells were built to evaluate various aspects of the baseline design. One 24 Ah negative-limited cell (versus 36 Ah positive electrode capacity) incorporated perforated sheet particle retainers and a 1.8 mm thick $\text{MgO}/\text{electrolyte}$ pressed pellet separator. Results indicated the need for improved (less restrictive) particle retainers and the possible need for higher purity (lower SiO_2 content) FeS_2 . The negative electrode capacity appeared to be lowered by loss of lithium to the SiO_2 . A second cell, void of particle retainers, demonstrated improved utilization, higher capacity, and lower impedance. A third cell was built to evaluate the thinner (1.2 mm thick) $\text{MgO}/\text{electrolyte}$ pressed pellet. This cell incorporates particle retainers.

Two 4-cell bipolar LiAl/FeS_2 stacks were fabricated to develop and refine stack assembly processes for cells that employ all molybdenum hardware. The first stack employed cells with under-sized $\text{MgO}/\text{electrolyte}$ pellets, high SiO_2 content FeS_2 , and non-optimal particle retainers. Stack integration and

final assembly was accomplished using TIG welding of the exposed edges of the molybdenum rings. Electrolyte leakage from these edge welds was observed during subsequent testing, indicating the need for further improvements in the final assembly process. This stack operated for 200 cycles and 1000 hours at 415°C. All four cells remained operational throughout the test, but one cell had a high self-discharge rate, which limited the capacity of the stack. Use of the under-sized separator pellets is the most likely source of variable performance among the cells. This stack is currently undergoing post-test tear-down and analysis.

The second 4-cell stack employs properly-sized separator pellets, a lower SiO₂ content FeS₂, but the same non-optimal particle retainers. An improved final assembly process was developed, that employs a post-weld braze using Hastalloy B. The braze was used to fill the gaps in the TIG weld and provide a leak-free Mo-ring/Mo-ring joint. To date, this stack has operated for 300 cycles and 2075 hours at 415°C. Also, it has been subjected to seven thermal cycles. One of the cells is exhibiting some capacity loss, but all four cells remain operational.

A materials database is being developed for the Li-alloy/FeS₂ program. This database will include relevant chemical and physical properties for electrodes, separators, electrolytes, seals, and coating systems for hardware materials. In addition, the database is designed to track the construction details for each cell and provide test and post-test summaries for hardware. One purpose for the database is to facilitate transfer of this technology to industrial developers. Also, our in-house program will benefit by documenting our present knowledge base and information needs. Agreement on content and format for the database was reached through a series of group discussions. The database is divided into nine separate sections with a range of 10 to 30 entries per section. Single quantity entries are required in most instances, but graphical representations will be appended to the database in cases such as the change in an electrode property with depth-of-discharge. Collection of known information is now in progress. Where experimental data are needed, we are prioritizing the order in which the information will be generated. One of the high priority needs is obtaining physical properties data on the chalcogenide ceramics. One dozen dilatometry samples were prepared for use in determining thermal expansion properties of selected chalcogenides.

1.2 Li/FeS₂ Project Planning

Objective and Background

Due to a shift in R&D emphasis to high-performance bipolar Li/FeS₂ batteries, there exists a need to develop an R&D strategy and plan for developing Li/FeS₂ batteries. The objective of this task is to work cooperatively with the USABC and industrial developers to establish a credible R&D project plan for this technology.

Technical Progress and Status

ANL continued to work with the USABC and an industrial developer to refine detailed work plans for a 3-year joint industry/ANL R&D project to develop first-generation bipolar Li/FeS₂ stacks and modules. As part of this project, ANL will provide technology transfer of its baseline bipolar Li/FeS₂ cell and stack technology; technical support for industry's first-generation hardware design/development effort; R&D on advanced components for enhancing performance, extending life, and/or reducing cost in the second-generation hardware; and independent evaluation of the first-generation hardware deliverables from the industrial battery developer.

TASK AREA 2.0 NICKEL/METAL HYDRIDE SUPPORT

This task area describes the activities undertaken in support of the USABC effort to develop nickel/metal hydride (Ni/MH) batteries for electric vehicle applications. These responsibilities have evolved from continuing service on the Technical Advisory Committee (TAC). Specific duties include service on the Working Group for the Ni/MH program with the Ovonic Battery Company (OBC) and a similar role on the still evolving program for nickel electrode development.

2.1 OBC Program Support

Objective and Background

The objective of this task is to support the OBC's development program for high-performance nickel/metal hydride batteries. In addition to continuing evaluations of OBC hardware, ANL will utilize prior experience in the technical management of alkaline battery programs for DOE to play an active role in the Working Group that oversees the OBC program.

Performance projections for contemplated EV-size nickel/metal hydride batteries indicate that this technology can exceed the USABC mid-term goals for power, energy, and cycle life. Independent verification of this technology's potential first came from performance and life characterization tests conducted at ANL under DOE sponsorship. These tests were conducted initially on small cylindrical cells (<4 Ah) and subsequently on larger prismatic cells (>25 Ah). The collective results demonstrate performance superior to other alkaline nickel battery technologies and justify the continued development of the OBC technology.

Technical Progress and Status

ANL continued work on the establishment of a comprehensive evaluation program for the Ovonic Battery Company's (OBC) nickel/metal hydride technology. Negotiations between USABC and ANL began in earnest shortly after the OBC contract was signed in May. ANL's third draft of the statement-of-work, which was prepared during this period, was revised in accordance with USABC's desire for ANL to concentrate on the evaluation of OBC's Ni/MH technology only. This statement-of-work outlined ANL's support in the areas of hardware evaluation, post-test analysis, and TAC activities. Estimated costs for this support effort were developed. In September, agreement was reached on the statement-of-work, following a series of meetings and discussions. This agreement initially provides funding for evaluation of the Phase I OBC deliverables. Work on the CRADA to formalize this agreement has progressed to the final approval stage. As this quarter came to a close, the OBC Ni/MH evaluation CRADA was under review by DOE-Chicago.

Concurrently ANL worked to minimize delays in getting the Phase I OBC deliverables on test. ANL drafted the first detailed set of test plans. These drafts serve as the starting point for discussions with representatives of OBC and USABC. Beginning in early July, a series of meetings were held to discuss subsequent iterations of the test plans. Agreement on their content was reached in early September.

Evaluation of the first contract deliverables began on schedule as this quarter came to a close. Testing is proceeding in accordance with the test plans. In addition, cycle-life evaluations, initiated under DOE sponsorship, continued for three prismatic OBC cells.

The design of the Phase I prismatic cells was the subject of a review held at OBC on May 28. The new cell design is to serve as the basic test unit for subsequent development and was the primary topic of discussion at the review. The new design is a derivative of an earlier prismatic design with the major change being the cell container. This change is directed at achieving reduced cost and longer life. Also, the process steps to be followed during cell assembly were reviewed and a tour of improvements in OBC's production and testing facilities was provided.

Finally, ANL prepared an outline detailing step-by-step procedures for the post-test analysis of Ni/MH cells. The recommended analytical procedures were included as part of a presentation made at the September 1-2 TAC meeting held in Detroit. These procedures are discussed under Task 3.2 of this report.

2.2 Nickel Electrode Technology Support

Objective and Background

The objective of this task is to assist in the identification and development of high-performance cost-effective nickel electrodes for use in USABC-supported technologies. Over the years, ANL has had and continues to have an extensive involvement in nickel-electrode development. This experience base includes optimization of electrode design for Na/NiCl cells, elucidation of the mechanisms by which contaminants poison nickel electrodes in alkaline batteries, and analytical studies of electrode degradation for a variety of nickel-based batteries. This technical expertise will be used to identify alternative developers of this component and assess their capabilities to develop a better nickel electrode.

Cost reductions are essential to the successful commercialization of EV-size Ni/MH batteries. Sintered, electrochemically impregnated nickel-electrodes are presently the electrode of choice for most developers of nickel-alkaline batteries, because of their superior performance and durability. A significant cost savings could be realized by reducing the amount of inactive nickel and simplifying the method of electrode fabrication without adversely impacting electrode performance. To this end, ANL is actively supporting the TAC's search for alternative vendors for this key component.

Technical Progress and Status

In July, ANL was part of the TAC delegation that visited Inco's Toronto research center for a second time. Inco discussed their advances in materials fabrication that hold promise for nickel electrodes made by pasting $\text{Ni}(\text{OH})_2$ powders directly into foam substrates. This trip provided the first update on their in-house nickel-electrode development program since the September 1991 visit.

Inco's progress in developing foam substrates is impressive. Their foams are made by the same carbonyl process used to refine nickel ore. Also, the gaseous carbonyl process offers inherently greater "throwing power" than conventional electro-plating from an aqueous solution. Thus, the uniformity of deposition for Inco's foam is unmatched. In addition, this process offers greater latitude in optimization of the foam for an electrode substrate. Foams of greater thickness and/or smaller pore size can be readily produced. Presently, Inco is operating a small pilot line at their research facility that can produce rolls of 30-cm wide foams with a nominal porosity of 97 to 98%. A pilot plant at their Copper Cliffs refinery is already under construction.

Sound metallurgical bonding of the foam to more substantial current-carrying tabs is essential to good electrode design. Inco believes that they have the solution in a new high surface-area powder. Their 210 powder is used as a sintering additive. It readily bonds the foam to the solid tab without altering the properties of the foam. When tested under tension to failure, bonded specimens fail within the foam rather than at the interface. Also, Inco reported that the 210 powder has found limited use as a capacity enhancing additive to AB₅-type Ni/MH electrodes in flooded cells. Additions of 5 to 15 vol.% are said to increase capacity by 20 to 50%. It remains to be determined whether similar benefits are achievable with AB₂-type electrodes or in starved-electrolyte cells.

Inco has continued work on a low-cost process for making battery-grade Ni(OH)₂. Present work is directed toward a reduction in the NO₃ residue from 0.3% to less than 0.1%. Loading densities as high as 2.1 g/cm³ have been demonstrated, and utilizations of up to 90% are reported for high loading foam plaques. It appears probable that one or more of Inco's new materials will prove commercially viable for use in high-performance nickel electrodes.

TASK 3.0: EV BATTERY PERFORMANCE AND LIFE EVALUATION

Experimental evaluations and post-experimental examinations are conducted at ANL to provide insight into those factors that limit the performance and life of advanced battery technologies and to help identify the most-promising R&D approaches for overcoming these limitations.

3.1 Performance and Life Tests

Objective and Description

The purpose of this work is to conduct battery performance and life evaluations and provide battery developers, users, and R&D program managers with data for determining the progress being made in battery R&D programs, battery technology comparison, and system modeling. Standardized tests are used to characterize the performance of the cells and modules for EV applications. These include the verification of rated capacity and the measurement of (1) available energy vs. constant current and constant-power discharge rate, (2) available peak power vs. depth-of-discharge (DOD) for acceleration capability, (3) self-discharge losses vs. standtime, (4) sustained hill climbing capability, (5) available capacity vs. partial discharge operations, and (6) projected ranges for various vehicles and driving schedules. Life-cycle tests are conducted with simulated driving power profile discharges (SFUDS and UFUDS) to 80% DOD. Cell internal resistance, IR-free voltage, and peak power vs. DOD data are derived from the measured values of cell and module voltage and current during variable power discharges. During life testing, the effect of age on these parameters is evaluated.

Technical Progress and Status

During the period of April through September 1992, EV life tests were continued on three Ni/MH cells using SFUDS discharges to 80% DOD. Additional single cells and multi-cell modules were received from OBC in September to be tested for the USABC. Meetings of the USABC, OBC, and ANL were held in July and September to develop test plans for these deliverables. The test plans include calendar shelf-life tests, performance characterization tests (as per USABC BTP guidelines), and cycle life testing with SFUDS and UFUDS discharges to 80% DOD.

The progress and results of these ongoing tests are being disseminated to the USABC Ni/MH Working Group and OBC.

3.2 Post-Test Analyses

Objectives and Background

Comprehensive examinations are conducted on hardware deliverables that have completed testing. Post-test examinations identify existing and potential failure mechanisms, assess the reliability of hardware components, and correlate changes in performance with changes in electrode morphology and composition. This information measures the technical progress made by battery developers and provides an indication of needed design and/or material changes.

In order to evaluate the relative merits of the various battery systems, it is essential to know the problem areas associated with the development of a particular technology and the developer's effectiveness in devising and implementing solutions. Post-test analyses provide an independent and objective source

of such information. The findings help USABC and the technology's developer focus resources on the critical challenges facing this technology. Often this activity is performed as a joint ANL-developer effort.

Technical Progress and Status

No hardware was available for post-test analysis since USABC-sponsored testing only began during the final months of this reporting period.

A procedural outline was drafted in response to a TAC request to begin standardization of post-test procedures. Table 1 lists eleven general steps to be followed in the examination of any battery technology. These guidelines instruct the analyst to review all hardware documentation and to conduct diagnostic and non-destructive tests prior to selection of cells for full examination. It is recommended that a minimum of two cells, the strongest and the weakest, be examined from every failed module in order to derive comparative data. After tear-down inspection is completed, specific analyses are to be conducted on the key components within these cells. The level of analysis is to be guided by the preliminary diagnostics and tear-down findings. A comprehensive report is then prepared and distributed to the program manager and the developer for the full utility of post-test analysis to be realized.

The types of analyses to be performed are to a large degree technology-dependent since the supported technologies involve broad differences in chemistry, design, construction, and life-limiting failure mechanisms. Detailed procedures were developed for the Ni/MH, Na/S, and Li/FeS₂ systems. These procedures are presented in Tables 2, 3, and 4, respectively. Procedures followed by a question mark indicate that the procedure may be impractical for a given cell design or that the procedure has not been fully developed. In the case of Ni/MH modules, the cell-selection step precedes the non-destructive inspection step because the modular construction facilitates this ordering. Detailed seal studies are not required for this technology, since no ceramic bonds are made between cell components.

These procedural outlines were presented at the TAC meeting on September 1-2, 1992. The recommendation was made to prepare a similar procedural outline for lithium-polymer batteries. This task will be performed as more information becomes available for the proposed designs of the different developers.

3.3 Battery Test Procedure Tiger Team Support

Objective and Background

The Battery Test Procedure (BTP) Tiger Team was established to ensure uniform test procedures are used for the evaluation of USABC hardware. The team objectives are: 1) to establish standardized test procedures that will measure battery performance against existing USABC criteria, 2) to direct the implementation of the adopted procedures as part of the developers' internal programs and for evaluation of deliverables at independent testing laboratories, and 3) to develop minimum standards for the acquisition and reporting of test data. The team was formally established in September 1992 and is composed of regular TAC members and the testing managers from the national laboratories. Presently, ANL has two members on the ETP Tiger Team.

Technical Progress and Status

During September, ANL participated in both BTP meetings as well as the TAC meeting at which this Tiger Team concept was discussed and adopted. In these initial meetings, a complete nomenclature for USABC deliverables was devised, and specific tests were linked with specific USABC battery goals. For a number of these tests, procedures had already been developed by the Battery Testing Task Force, the DOE-sponsored antecedent to the present group. Other procedures need to be developed. ANL was assigned responsibility for drafting the Partial Discharge Test.

Reporting and data acquisition requirements received some discussion at the latter meetings. ANL prepared a summary of its data acquisition system and data storage capabilities. In addition, we drafted summary table formats for collecting the results of performance characterization tests. Other table formats were drafted to help track key performance parameters over cycle life. These draft summary tables will be discussed at future BTP meetings.

TABLE 1. GENERAL GUIDELINES FOR POST-TEST ANALYSIS

- 1. PRELIMINARY REVIEW**
- 2. DIAGNOSTIC CYCLES**
- 3. NON-DESTRUCTIVE INSPECTION**
- 4. CELL SELECTION**
- 5. TEAR-DOWN INSPECTION**
- 6. ELECTROLYTE STUDIES**
- 7. ELECTRODE STUDIES**
- 8. SEPARATOR STUDIES**
- 9. SEAL STUDIES**
- 10. STUDIES OF OTHER COMPONENTS**
- 11. DOCUMENTATION OF FINDINGS**

TABLE 2. POST-TEST ANALYSIS OF Ni/MH MODULES

Preliminary Review:	<ul style="list-style-type: none"> - Cell and Module Construction - Test History Data
Diagnostic Cycles:	<ul style="list-style-type: none"> - Final Cell Capacity, Voltage, and Impedance Checks - Reference Electrode Measurements ? - Termination in the Discharged State
Cell Selection:	<ul style="list-style-type: none"> - Representative 'Strong' Cell - Limiting Cell or All Failed Cells
Non-Destructive Inspection:	<ul style="list-style-type: none"> - Cell Weights and Dimensional Measurements - Thermographic Imaging (Cells with Internal Short-Circuits Only) - Pressure Retention Test for Case Leaks - Vent Septum Inspection
Tear-Down Inspection:	<ul style="list-style-type: none"> - Removal of Cell Lid and Disassembly of Electrode Stacks - Visual Examination of Electrodes, Separators, and Internal Connections - Electrode Dimensional Measurements - Wet Electrode and Separator Measurements - Macro-Photography - Electrolyte Extraction from Electrodes and Separators - Preparation of Samples for the Analyses Outlined Below
Electrolyte Studies:	<ul style="list-style-type: none"> - Specific Gravity Determinations - Atomic Absorption Spectroscopy for K^+, Li^+, and Impurity Cations - Two-Step Coulometric Titration for OH^- and CO_2^-
Electrode Studies:	<ul style="list-style-type: none"> - Bulk Microstructural and Phase Analyses <ul style="list-style-type: none"> Optical Microscopy X-ray Diffraction (MH Electrodes Only) Intrusion Porisimetry - Surface Characterization and Element Distributions <ul style="list-style-type: none"> Scanning Electron Microscopy Energy Dispersive Spectroscopy Auger Electron Spectroscopy (MH Electrodes Only)
Separator Studies:	<ul style="list-style-type: none"> - SEM for Fiber Degradation - Tensile Strength Test ?
Seal Studies:	<ul style="list-style-type: none"> - Not Applicable
Studies of Other Components:	<ul style="list-style-type: none"> - Required Analytical Tools When Macro-Observations Indicate a Problem
Documentation of Findings:	<ul style="list-style-type: none"> - Post-Test Analysis Report w/ Text, Illustrations, and Data Sheets

TABLE 3. POST-TEST ANALYSIS OF Na/S MODULES

Preliminary Review:	<ul style="list-style-type: none">- Cell and Module Construction- Test History Data
Diagnostic Cycles:	<ul style="list-style-type: none">- Final Module (and, if Possible, Sub-Unit) Capacity, Voltage, and Impedance Checks- Termination in the Charged State and Cool Down
Non-Destructive Inspection:	<ul style="list-style-type: none">- Removal of Module from Thermal Enclosure- Inspection for Leakage via Container or Seals- Cold Voltage Measurements for each Cell or String of Cells- Radiography for Cells (Strings) with Low Voltages
Cell Selection:	<ul style="list-style-type: none">- Representative 'Strong' Cell- Limiting Cell or All Failed Cells
Tear-Down Inspection:	<ul style="list-style-type: none">- Sectioning to Separate Cell Top w/ Seals from Cell Proper- Continued Sectioning to Obtain Desired Electrolyte, Container, and Positive Electrode Samples- Excess Sodium Removal from Samples (Mechanically and/or Alcohol Dissolution)- Macro-Photography- Preparation of Samples for the Analyses Outlined Below
Electrolyte Studies:	<ul style="list-style-type: none">- Fracture Analysis via Scanning Electron Microscopy- Electrolyte Contamination via Energy Dispersive Spectroscopy
Electrode Studies:	<ul style="list-style-type: none">- Electrode Morphology and Corrosion Products via Optical Microscopy- Corrosion and Polysulfide Phase Identification via X-ray Diffraction- Element Distributions via Energy Dispersive Spectroscopy
Separator Studies:	<ul style="list-style-type: none">- Not Applicable
Seal Studies:	<ul style="list-style-type: none">- Assessments of Bond Integrity and Chemical Degradation Using the Methods Outlined under Electrode Studies
Studies of Other Components:	<ul style="list-style-type: none">- Required Analytical Tools When Macro-Observations Indicate a Problem
Documentation of Findings:	<ul style="list-style-type: none">- Post-Test Analysis Report w/ Text, Illustrations, and Data Sheets

TABLE 4. POST-TEST ANALYSIS OF LI/FES₂ STACKS

Preliminary Review:	<ul style="list-style-type: none">- Cell and Module Construction- Test History Data
Diagnostic Cycles:	<ul style="list-style-type: none">- Final Stack (and, if Possible, Cell) Capacity, Voltage, and Impedance Checks- Termination in the Charged State and Cool Down
Non-Destructive Inspection:	<ul style="list-style-type: none">- Removal of Stack from Container- Stack Weight and Height Measurements- Inspection for Leakage via Cracks in Welds or Peripheral Seals- Radiography for Internal Electrode Alignment- Cold Resistance Measurements to Identify Failed Cells (A Grinding Pass to Expose the Bipolar Plates Maybe Necessary if the Stack Has No Cell Voltage Leads.)
Cell Selection:	<ul style="list-style-type: none">- Representative 'Strong' Cell- Limiting Cell or All Failed Cells
Tear-Down Inspection:	<ul style="list-style-type: none">- Thermographic Imaging (Cells with Internal Short-Circuits Only) ?- Grinding of Perimeter Welds to Free Selected Cells- Encapsulation of Selected Cells in E₁oxy- Reiterative Sectioning and Resistance Readings until Samples Are Obtained of Short-Circuits in Failed Cells and Representative Sections of Strong Cells- Thickness Measurements of Electrodes and Separators- Macro-Photography- Preparation of Samples for the Analyses Outlined Below
Electrolyte Studies:	<ul style="list-style-type: none">- Analytical Determinations Are Generally Part of Electrode or Separator Studies.
Electrode Studies:	<ul style="list-style-type: none">- Electrode Morphology and Corrosion Reactions via Optical Microscopy- Phase Identification via X-ray Diffraction- Element Distributions via Energy Dispersive Spectroscopy- Lithium Distribution via Auger Electron Spectroscopy (When Required)
Separator Studies:	<ul style="list-style-type: none">- Assessments of Active-Material Deposition/Infiltration Using the Methods Outlined under Electrode Studies
Seal Studies:	<ul style="list-style-type: none">- Assessments of Bond Integrity and Chemical Degradation Using the Methods Outlined under Electrode Studies
Studies of Other Components:	<ul style="list-style-type: none">- Required Analytical Tools When Macro-Observations Indicate a Problem
Documentation of Findings:	<ul style="list-style-type: none">- Post-Test Analysis Report w/ Text, Illustrations, and Data Sheets

END

DATE
FILMED
3/19/93