PNL-8502
UC-721

FIRST-ORDER STUDY OF PROPERTY/COMPOSITION
RELATIONSHIPS FOR HANFORD WASTE
VITRIFICATION PLANT GLASSES

G. F. Piepel
P. R. Hrma
S. O. Bates
M. J. Schweiger
D. E. Smith

Date published: January 1993
Date work completed: May 1991

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

MASTER

PREFACE

This report contains the results from the initial stage of the Hanford Waste Vitrification Project (HWVP) Composition Variability Study (CVS). This initial stage of the study was conducted in 1989 and 1990, and is referred to as CVS-I. This report is a cleared-for-publication version of the May 1991 internal project report which originally documented the CVS-I results.

Because this is essentially a May 1991 report being published in January 1993, some discussions, terminology, and references may not be current due to developments during the intervening 19 months. Further, the results themselves have been superseded by results from the second stage of the study (CVS-II). The purpose in publishing the report at this time is to provide a publicly referencable account of the CVS-I study, because of its importance in laying the foundation for CVS-II.

ABSTRACT

A first-order composition variability study (CVS-I) was conducted for the Hanford Waste Vittrification Plant (HWVP) program to preliminarily characterize the effects on key glass properties of variations in selected glass (waste and frit) components. The components selected were SiO_2 , B_2O_3 , Al_2O_3 , Fe_2O_3 , ZrO_2 , Na_2O , Li_2O , CaO , MgO , and Others (all remaining waste components). A glass composition region was selected for study based on the expected range of glass compositions and the results of a previous series of scoping and solubility studies. Then, a 23-glass statistically-designed mixture experiment was conducted and data obtained for viscosity, electrical conductivity, glass transition temperature, thermal expansion, crystallinity, and durability [Materials Characterization Center (MCC-1) 28-day leach test and the 7-day Product Consistency Test (PCT)]. These data were modeled using first-order functions of composition, and the models were used to investigate the effects of the components on glass and melt properties. The CVS-I data and models will also be used to support the second-order composition variability study (CVS-II).

SUMMARY

A first-order composition variability study (CVS-I) was conducted for the Hanford Waste Vitrification Plant (HWVP) program to characterize the effects on key glass properties of variations in selected glass (waste and frit) components. A glass composition region was selected for study based on the expected range of glass compositions and the results of a previous series of scoping and solubility studies. Then, a statistically-designed 10-component mixture study was conducted and the data modeled to provide a first-order characterization of variations in glass and melt properties as a function of glass composition. The data and models generated during the study will support the second-order composition variability study (CVS-II), HWVP feed pretreatment specifications, feed makeup activities, formulation of radioactive glasses, and the development of the HWVP process and product models to be used in the HWVP Waste Form Qualification (WFQ) effort.

The following glass (waste and/or frit) components were varied in CVS-I: SiO_2 , B_2O_3 , Al_2O_3 , Fe_2O_3 , ZrO_2 , Na_2O , Li_2O , CaO , MgO , and Others (all remaining waste components). A test matrix of 19 distinct glass compositions and 4 replicates was selected using statistical mixture experiment techniques. The glass and melt properties measured were viscosity, electrical conductivity, glass transition temperature, thermal expansion, crystallinity, and durability based on the Materials Characterization Center (MCC-1) 28-day leach test and the 7-day Product Consistency Test (PCT). The results were used to fit empirical first-order mixture models. These models explain much of the variation in the properties of interest (R^2 values range from approximately 0.75 to 0.98), but have statistically significant lack-of-fits. The lack-of-fit can be addressed by reducing the size of the composition region studied in the second-order CVS (CVS-II) so as to eliminate compositions with properties far from acceptable limits, and by including second-order terms in the property models. Although the first-order mixture models had statistically significant lack-of-fits, they were deemed adequate for preliminary use in understanding the effects of the 10 components on glass and melt properties, defining the composition region for CVS-II, and evaluating the effects of TRU

recycle waste stream additions to the HW-39-4 NCAW glass composition. The following major conclusions were reached:

- Although some of the nine glass components (SiO_2 , B_2O_3 , Al_2O_3 , Fe_2O_3 , ZrO_2 , Na_2O , Li_2O , CaO , and MgO) had little or no effect on certain glass and melt properties, each component had a significant effect on at least one property. Hence, it is not advisable to reduce the number of components to be studied in CVS-II.
- The "Others" component, with a mix of nonradioactive minor components corresponding to Neutralized Current Acid Waste (NCAW), had minor-to-negligible effects on all glass and melt properties. Selected glasses with "Others" mixes corresponding to the Neutralized Cladding Removal Waste (NCRW), Plutonium Finishing Plant (PFP), and Complexant Concentrate (CC) wastes will be tested during CVS-II.
- The composition region studied in CVS-I includes compositions with one or more property values considerably outside the ranges deemed acceptable for HWVP operation. This occurs when certain components are at high and/or low levels simultaneously, and is not due to the ranges of individual components being too wide.
- Waste glass viscosity and electrical conductivity can be adjusted to a desirable level by balancing the content of SiO_2 , B_2O_3 , and Li_2O in such a way that high durability of the product is maintained and crystallization in the melter is avoided. The first-order mixture models for viscosity and electrical conductivity are adequate preliminary tools for eliminating compositions that will not be processable in the HWVP melter.
- A highly nonlinear low-durability region of compositions was found in the B_2O_3 -rich and Al_2O_3 -poor portion of the composition range tested. The CVS-I first-order elemental release models are not sufficient to accurately predict durability within this region, but can be used to avoid the area during CVS-II testing.
- The multiple-component constraints used during CVS-I to eliminate glasses with liquidus temperature higher than 1050°C were not completely successful. The constraints have been improved based on CVS-I results, but they cannot substitute for mathematical models developed from liquidus temperature data and/or existing knowledge. Progress towards the development of such models is expected during CVS-II, but the highly nonlinear nature of the liquidus temperature as a function of composition will likely preclude using the second-order mixture models intended for use with other property data. However, it may be possible to develop separate first-order models from liquidus temperature data for each primary crystalline phase found in the test glasses.
- Analyzed glass compositions compared well with target compositions except for a number of indications of bias. In some cases the bias

appeared to be due to the analytical process, while in others it could be due to phase separation. It was decided to use target compositions in all data analyses.

- Models that express viscosity and electrical conductivity data as simultaneous functions of temperature (via Fulcher and Arrhenius equations, respectively) and glass composition (via empirical mixture models) were investigated as alternatives to models that express these properties at 1150°C as functions of glass composition alone. The former models predict viscosity and electrical conductivity at 1150°C nearly as well as the latter models, and have the added flexibility of being able to predict properties at other temperatures as well. The combined temperature and glass composition modeling approach will be used during CVS-II.

ACKNOWLEDGMENTS

The authors acknowledge the technical efforts and contributions of the following individuals: D. E. Larson for programmatic guidance, M. J. Schweiger and D. E. Smith for glass preparation and physical measurements, N. R. Gordon for glass transition temperature measurements, N. T. Saenz for optical microscopy, J. E. Coleman for scanning electron microscopy and EDX. F. T. Hara, T. G. Walker, D. L. Thomas, D. E. Rinehart, and L. M. Thomas are acknowledged for chemical analyses of glass and leachate compositions. Staff at Westinghouse Hanford Company and U.S. Department of Energy Richland Field Office (DOE-RL) are acknowledged for reviewing the document and DOE-RL for funding the activity.

CONTENTS

PREFACE	iii
ABSTRACT	v
SUMMARY	vii
ACKNOWLEDGMENTS	xi
1.0 INTRODUCTION	1.1
1.1 HWVP OVERVIEW	1.1
1.2 CVS OVERVIEW	1.2
2.0 OBJECTIVES	2.1
2.1 OVERALL CVS OBJECTIVES	2.1
2.2 CVS-I OBJECTIVES	2.1
3.0 MELT AND GLASS PRODUCT REQUIREMENTS	3.1
3.1 VISCOSITY	3.1
3.2 ELECTRICAL CONDUCTIVITY	3.3
3.3 PHASE BEHAVIOR	3.3
3.4 GLASS TRANSITION TEMPERATURE AND THERMAL EXPANSION	3.4
3.5 DURABILITY	3.4
4.0 TECHNICAL APPROACH	4.1
4.1 COMPOSITION REGION DEFINITION	4.1
4.1.1 Glass Components	4.1
4.1.2 Component Constraints	4.6
4.1.3 Iterative Development of the Composition Region	4.7
4.2 SELECTION OF TEST COMPOSITIONS	4.9
4.2.1 Test Matrix Generation	4.9
4.2.2 First-Order CVS-I Test Matrix	4.11

4.3	MEASUREMENT OF GLASS PROPERTIES	4.13
4.3.1	Glass Fabrication	4.14
4.3.2	Viscosity	4.14
4.3.3	Electrical Conductivity	4.15
4.3.4	Phase Behavior	4.16
4.3.5	Glass Transition Temperature	4.16
4.3.6	Durability	4.16
4.4	EMPIRICAL MODELING	4.18
4.5	MODEL VALIDATION	4.19
4.6	COMPONENT EFFECTS	4.20
4.7	QUALITY ASSURANCE	4.21
5.0	RESULTS AND DISCUSSION	5.1
5.1	GLASS PROPERTIES	5.1
5.1.1	Viscosity	5.1
5.1.2	Electrical Conductivity	5.3
5.1.3	Glass Transition Temperature	5.6
5.1.4	Thermal Expansion Coefficients	5.6
5.1.5	Glass Crystallization	5.12
5.1.6	Glass Durability	5.15
5.2	CORRELATIONS AMONG GLASS PROPERTIES	5.26
5.3	FITTED LINEAR MIXTURE MODELS	5.31
5.3.1	Model Coefficients and Goodness-of-Fit Statistics	5.31
5.3.2	Model Validation	5.36
5.4	CVS-II COMPOSITION REGION AND THE QCR	5.43
5.4.1	CVS-II Components and Composition Region	5.43

5.4.2	Qualified Composition Region	5.43
6.0	EFFECT OF HWVP RECYCLE STREAMS ON GLASS PROPERTIES	6.1
7.0	CONCLUSIONS AND RECOMMENDATIONS	7.1
7.1	CONCLUSIONS	7.1
7.1.1	Applicability of Linear Mixture Models	7.1
7.1.2	Viscosity	7.1
7.1.3	Electrical Conductivity	7.2
7.1.4	Glass Transition Temperature and Thermal Expansion	7.2
7.1.5	Crystallization	7.2
7.1.6	Elemental Release	7.3
7.1.7	Effect of Li_2O	7.3
7.1.8	Recycle Addition	7.3
7.2	RECOMMENDATIONS	7.4
7.2.1	Recommendations for CVS-II	7.4
7.2.2	Recommendations on Use of CVS-I Results	7.5
8.0	REFERENCES	8.1
APPENDIX A:	COMPARISON OF TARGET AND ANALYZED COMPOSITIONS FOR CVS-I GLASSES AND LONGER-TERM UNCERTAINTY IN ANALYZED COMPOSITIONS	A.1
APPENDIX B:	CVS-I VISCOSITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE FLUCHER EQUATION	B.1
APPENDIX C:	CVS-I ELECTRICAL CONDUCTIVITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE ARRHENIUS EQUATION	C.1
APPENDIX D:	NORMALIZED ELEMENTAL RELEASES AND STANDARD DEVIATIONS FROM DUPLICATE MCC-1 AND PCT LEACH TESTS	D.1
APPENDIX E:	HWVP MEASUREMENT AND TEST EQUIPMENT (M&TE) LIST	E.1

FIGURES

5.1	Predicted Component Effects on Viscosity at 1150°C Relative to the HW-39-4 Composition	5.4
5.2	Predicted Component Effects on Temperature at Which Viscosity is 10 Pa.s Relative to the HW-39-4 Composition	5.5
5.3	Predicted Component Effects on Electrical Conductivity Relative to the HW-39-4 Composition	5.7
5.4	Predicted Component Effects on Glass Transition Temperature Relative to the HW-39-4 Composition	5.9
5.5	Predicted Component Effects on Thermal Expansion Coefficient for Solid Glass Relative to the HW-39-4 Composition	5.10
5.6	Predicted Component Effects on Thermal Expansion Coefficient for Molten Glass Relative to the HW-39-4 Composition	5.11
5.7	Predicted Components Effects on MCC-1 Normalized Release Relative to the HW-39-4 Composition	5.21
5.8	Predicted Component Effects on MCC-1 Normalized Release Relative to the HW-39-4 Composition	5.22
5.9	Scatterplot of Normalized B Releases from 7-Day PCT and 28-Day MCC-1 Leach Tests for the CVS-I Glasses	5.25
5.10	Scatterplot of Log Transformed Normalized B Releases from 70Day PCT and 28-Day Leach Tests for the CVS-I Glasses	5.26
5.11	Predicted Component Effects on PCT Normalized B Release Relative to the HW-39-4 Composition	5.27

TABLES

3.1	HWVP Acceptability Criteria for Glass Properties	3.2
4.1	Approximate Number of Test Melts Required for Second-Order Model Fitting and Evaluation as a Function of the Number of Components	4.2
4.2	Oxide Compositions of NCAW/87 Waste and Substitute Waste for CVS-I	4.3
4.3	Preliminary Compositions for NCRW, PFP, and CC Wastes Compared to NCAW	4.4
4.4	Composition of "Others" for CVS-I	4.5
4.5	Composition Region Studied in CVS-I	4.8
4.6	Matrix of Test Compositions for CVS-I	4.11
4.7	Pairwise Correlations Among Glass Components and Batch Membership	4.13
4.8	HWVP Open Canister Turntable Simulated Centerline Cooling Profile	4.17
5.1	Property Transformations Indicated by Statistical Investigation of the CVS-I Data	5.1
5.2	CVS-I Data for Temperature at Which Viscosity is 10 Pa.s, Viscosity at 1150°C, and Electrical Conductivity at 1150°C	5.2
5.3	CVS-I Data for Glass Transition Temperature, Thermal Expansion Coefficient for Solid Glass, Thermal Expansion Coefficient for Molten Glass, and Liquidus Temperature	5.8
5.4	X-Ray Diffraction Analysis of CVS-I Heat Treated Glasses	5.13
5.5	Si, B, Li, Na, Mo, and Cs Normalized Releases and Leachate pHs Averaged Over Duplicate 28-Day MCC-1 Leach Tests of the CVS-I Glasses	5.17
5.6	Si, B, Li, Na, Mo, and Cs Normalized Releases and Leachate pHs Average Over Duplicate 7-Day PCT Leach Tests of the CVS-I Glasses	5.24

5.7	Normalized Elemental Releases from Repeat Tests on Three Glasses	5.28
5.8	Pairwise Correlations Among Untransformed Glass Properties	5.29
5.9	Pairwise Correlations Among Transformed Glass Properties	5.30
5.10	Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to T_{10} , η_{1150} , ϵ_{1150} , T_g , α_s , and α_m	5.32
5.11	Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models to PCT Normalized Elemental Releases	5.33
5.12	Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to MCC-1 Normalized Elemental Releases from All CVS-I Glasses	5.34
5.13	Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to MCC-1 Normalized Elemental Releases After Deleting the High Release Data Corresponding to Glasses CVS1-4,6,9,13,15,21	5.35
5.14	Standard Deviations of Untransformed and Transformed Glass and Melt Property Data from Replicate Glasses	5.37
5.15	Glass Compositions Used to Assess Predictive Ability of Fitted Linear Mixture Models	5.38
5.16	Comparison of Measured Property Values to Predicted Values from the Fitted Linear Mixture Models for Compositions in Table 5.15	5.39
6.1	Content of Feed to Slurry Mix Evaporator Tank with TRU Recycle Streams	6.2
6.2	Composition of SBS Process Solids, Zeolite, Diatomaceous Earth, and DWTT Chemicals	6.3
6.3	Predicted Values of T_{10} and ϵ_{1150} for Multiple Nominal Additions of Treated SBS Recycle Waste to the HW-39-4 Reference Glass	6.4

1.0 INTRODUCTION

1.1 HWVP OVERVIEW

The Hanford Waste Vitrification Plant (HWVP) will convert selected Hanford defense high-level and transuranic wastes to a vitrified form (borosilicate glass) for final disposal in a geologic repository. For pretreated waste streams are planned to be vitrified by HWVP: Neutralized Current Acid Waste (NCAW), Neutralized Cladding Removal Waste (NCRW), Plutonium Finishing Plant (PFP) waste, and Complexant Concentrate (CC) waste. The chemical compositions of these wastes differ. Also, the feed delivered to the HWVP for each specific waste type is expected to vary in composition due to non-uniform mixing of the million gallon tank contents and tank-to-tank differences. The resulting HWVP glass product will therefore vary around the nominal glass composition(s).

Changes in glass composition affect melt viscosity, electrical conductivity, and phase behavior. These properties determine the processability of the glass in the melter. Glass composition also affects chemical durability, thus impacting the acceptability of the glass product for isolation in a geologic repository.

The minimum requirements that the waste form must meet to be acceptable for disposal in a geologic repository are specified by the Waste Acceptance Preliminary Specifications (WAPS). These specifications were prepared by the Waste Acceptance Committee (WAC) for the Defense Waste Processing Facility (DWPF) and by the U.S. Department of Energy (DOE) Office of Civilian Radioactive Waste Management for the West Valley Demonstration Project (WVDP). A preliminary HWVP Waste Form Qualification (WFQ) Plan (Nelson 1988) based on the DWPF WAPS was used in preparing the test plan for this study. The WAPS is being revised by the DOE Yucca Mountain Project Office (YMPO) and will generically apply to all waste glass producers.

Where possible, HWVP compliance with the WAPS will be achieved by process control and direct measurement of process or product variables. Direct measurements will be limited in scope due to the remote operation and shielding requirements of the HWVP process and product. Where direct measurements

are not possible or limited (e.g., glass product composition), translation of available direct measurements (e.g., feed composition) to the required WAPS specifications will be achieved through process and product models integrated into the plant process control system. This will reduce the number of glass samples to be taken to assure product compliance. Data from the HWVP Composition Variability Study (CVS) and other testing will be used to develop product and process models. These models and actual plant operating data will then be the basis for demonstrating product compliance with the WAPS requirements during cold verification and hot operation. Control of the process will be monitored by analyses of samples taken at various points in the process and evaluated using the product and process models.

1.2 CVS OVERVIEW

The goals of the CVS conducted by Pacific Northwest Laboratory^(a) are to develop glass and melt property models as functions of composition, and specify the region of glass compositions that will satisfy with high confidence the requirements on physical and chemical properties of the glass. This region will be referred to as the **Qualified Composition Region (QCR)**. HWVP will operate within this region of acceptable compositions so as to produce an acceptable waste form. These goals will be achieved by conducting statistically-planned composition variability testing to characterize the effects of variations of selected glass components on the glass properties of interest.

The CVS was planned in two parts, referred to here as CVS-I and CVS-II. CVS-I was planned as a first-order study that would provide for fitting first-order models in composition to property data gathered at the extremes of the composition region of interest. CVS-II is a second-order study that will provide for fitting second-order models in composition to property data both at the extremes and on the interior of a refined (based on CVS-I results) composition region of interest. This report presents the results of CVS-I.

(a) Operated for the U.S. Department of Energy by Battelle Memorial Institute under Contract DE-AC06-76RLO 1830.

CVS-I involved testing 23 glass compositions (including four replicates). Viscosity, electrical conductivity, glass transition temperature, thermal expansion, crystallinity, and leach test data were obtained and used to fit empirical first-order mixture models. These models were used to understand the effects of the major glass components on the properties, and will be used in planning CVS-II.

2.0 OBJECTIVES

2.1 OVERALL CVS OBJECTIVES

The general objective of the CVS (i.e., CVS-I and CVS-II) is to conduct composition variation experiments and collect melt and glass property data to provide a basis for waste form qualification, product and process control activities, and compliance with the WAPS. The related specific objectives are to:

- Develop first- and second-order empirical mixture models expressing the glass and melt properties as functions of composition. Second-order mixture models will account for interactive and nonlinear blending effects of the glass components on glass and melt properties.
- Specify the **qualified composition region (QCR)** for acceptable HWVP melter processability and compliance with the WAPS requirements. This will establish a composition region within which compositions will be selected for time-temperature-transformation (TTT) diagrams, pilot-scale melter runs, and HWVP cold-testing runs.
- Provide input for graphical display of properties of glass prepared by mixing HWVP waste streams, recycle streams, and frits.
- Provide input to the HWVP feed specification and performance assessment for each type of waste (based on information available to date).
- Provide methodology for preparation of acceptable radioactive glasses from core samples and available feed for bench-scale testing.

2.2 CVS-I OBJECTIVES

The objectives for CVS-I were more specific than the overall CVS objectives due to the "start of the study" nature of CVS-I. The CVS-I objectives were to:

- Identify those components that affect the glass and melt properties.
- Investigate a composition region including unacceptable as well as acceptable glasses to identify the boundary of acceptability.
- Develop first-order mixture models and assess their adequacy for modeling glass and melt properties as a function of composition.
- Refine the number of components and/or the composition region studied in CVS-I as necessary for CVS-II.

3.0 MELT AND GLASS PRODUCT REQUIREMENTS

There are two types of melt and glass property requirements of concern in these studies: 1) those required for HWVP melter processability, and 2) those required by the WAPS for repository acceptance of the glass. The processing properties affect melter operation and glass pouring. HWVP melter processing requirements have been established for viscosity, electrical conductivity, liquidus temperature, and phase behavior (crystallization and phase separation). The WAPS impose limitations on durability, and require that glass transition temperature and chemical and phase stability information be reported. The acceptability criteria for glass processing and product properties are listed in Table 3.1.

Some glass and melt properties, such as the glass transition temperature (T_g) and time-temperature-transformation (TTT), do not currently have any limitations imposed by the WAPS, but are required by the WAPS to be reported. The results of optical and x-ray diffraction (XRD) examinations of quenched and heat treated glasses (simulated canister centerline cooling) and the glass transition temperature data are included in this report to provide general characteristics of the CVS-I glasses. The TTT measurements and the examination of the effect of heat treatment on glass durability are currently planned to be conducted after the CVS is completed. The glass and melt properties measured during CVS-I are discussed in the following sections.

3.1 VISCOSITY

Melting of industrial glasses typically proceeds at 10 Pa·s (100 poise).^(a) This melting viscosity has been confirmed for waste glasses by tests in pilot- and engineering-scale melters (Hagy et al. 1974; Chick, Swanson, and Goldman 1984). The viscosity of the waste glass at the nominal melting temperature (1150°C) should be between 2 and 10 Pa·s for acceptable melter operation and glass pouring. This range approximately corresponds to

(a) The Standard International unit for viscosity is Pa·s. The older unit, poise, is no longer accepted by international journals. Note that 1 Pa·s = 10 poise.

TABLE 3.1. HWVP Acceptability Criteria for Glass Properties

<u>Property</u>	<u>Acceptability Criteria</u>
Viscosity at 1150°C	2 - 10 Pa·s
Electrical conductivity at 1150°C	18 - 50 S/m ^(a)
Liquidus temperature	≤ 1050°C
Phase separation	No separation of molten salts
Dissolution rate in deionized water	
MCC-1	≤ 1 g/m ² ·day ^(b)
PCT	≤ EA glass (TBD) ^(c)
Glass transition temperature ^(d)	Descriptive
Devitrification during cooling ^(e)	Descriptive
Other processability aspects ^(f)	

(a) S = Siemens = Ohm⁻¹.

(b) Normalized elemental release averaged over a 28-day period.

(c) The in-progress revision of WAPS by DOE-YMPO specifies that elemental releases of boron, lithium, and sodium be less than that of the DWPF Environmental Assessment (EA) glass. Numerical limits for the elemental releases have not yet been determined.

(d) The Waste Acceptance Preliminary Specifications (WAPS) require that glass transition temperature be reported, however there are no specified acceptability limits.

(e) The WAPS has not set a limit on the amount of crystalline material in the glass, but does require that crystalline material expected to be present be characterized.

(f) The CVS does not address other processability aspects, such as feed requirements to limit foaming and guarantee a stable cold cap that melts at an acceptable rate. Other testing outside of the CVS will address such aspects.

to the range from 1050 to 1150°C for T_{10} , the temperature at which viscosity is 10 Pa·s. The upper limits for T_{10} and viscosity are identical and the lower limits are approximately the same (a glass with a T_{10} at 1050°C has a viscosity of 2 to 4 Pa·s at 1150°C). If the viscosity is outside the range of 2 to 10 Pa·s at 1150°C, processing problems may be encountered in the melter.

Glass with viscosity lower than 2 Pa·s tends to penetrate into the melter refractory blocks and excessively corrodes melter walls. Glass with viscosity higher than 10 Pa·s results in a slow melting rate, is difficult to pour from the melter, and may not form a consolidated monolith in the canisters.

3.2 ELECTRICAL CONDUCTIVITY

In joule-heated ceramic melters designed at PNL, the electrical conductivity of the glass melt should be 18 to 50 S/m at 1150°C.^(a) An electrical conductivity lower than 18 S/m at the melting temperature would require a higher voltage across the electrodes, resulting in conduction within the melter refractory. If the electrical conductivity is too high, the current required to heat the glass will exceed the recommended maximum density for the melter electrodes, which could shorten electrode life. Electrical conductivity limits for the Defense Waste Processing Facility (DWPF) melter are 40 to 110 S/m.

3.3 PHASE BEHAVIOR

Phase behavior includes both processing and product characteristics. Crystallization and liquid-liquid separation affect glass processability. Additional crystallization may occur during cooling of glass in canisters. The temperature at which the melt is in equilibrium with the primary crystalline phase is called the liquidus temperature (T_L). HWVP adopted the DWPF criteria for T_L which specifies an upper limit of 1050°C. Only minor crystalline phases such as the insoluble noble metals or their oxides can be present. Otherwise, no excessive crystallization or phase separation should occur in the glass melter. The presence of insoluble and residual solid phases may increase the rate at which a sludge forms on the bottom of the melter, clog areas within the melter, and short the melter electrodes. Radionuclides such as cesium may be concentrated in a separated melt phase such as an alkali-sulfate melt. This phase may exhibit excessive volatility causing off-gas system clogging, electrical shorting, and increased corrosion of melter walls

(a) J. E. Minor, personal communication to R. W. Gurley (1984).

and electrodes. Phase separation of the glass phase during cooling will impair durability if the low-durability phase is connected. Crystallization can also affect product durability.

3.4 GLASS TRANSITION TEMPERATURE AND THERMAL EXPANSION

The glass transition temperature (T_g) characterizes the transformation from an equilibrated melt to a "frozen" glass structure. At the glass transition temperature, thermal expansion, heat capacity, and other properties change abruptly. There are no restrictions on T_g (WAPS only requires that it be reported), so it will not play a role in defining the QCR. Thermal expansion coefficients of solid (α_s) and molten (α_m) glass are obtained as by-products of the T_g measurement, and therefore are also reported. Despite their descriptive role, thermal expansion coefficients are important for glass processing. Thermal expansion of molten glass affects convection currents in the melter; these currents control the heat transfer from molten glass to the cold cap. Thermal expansion of solid glass determines the extent of internal stresses produced during cooling.

3.5 DURABILITY

The WAPS will require HWVP to document the normalized elemental releases of the HWVP waste form. The DWPF WAPS currently requires that the waste form be capable of limiting normalized elemental release rates for sodium, silicon, boron, cesium-137, and uranium-238 to less than a $1.0 \text{ g/m}^2\cdot\text{day}$ averaged over a 28-day MCC-1 test (MCC 1983). In other words, the preliminary specification on durability is that normalized elemental releases determined by the 28-day MCC-1 test should not exceed 28 g/m^2 . This specification is currently being revised to specify the 7-day Product Consistency Test (PCT), with the limiting release defined as that of the glass specified in the DWPF Environmental Assessment waste form selection document (U.S. DOE 1982). Once the WAPS revision is complete and EA glass release limits are established, the QCR can be defined with respect to glass durability. In this study, 28 g/m^2 during the 28-day MCC-1 test was used as the limiting normalized elemental release.

The MCC-1 dissolution test was issued by the Materials Characterization Center (MCC).^(a) The PCT (Product Consistency Test 1989) was proposed by DWPF to be used in lieu of the MCC-1 test method in hot-cell applications and WFQ. Testing CVS glasses with both the MCC-1 test and the PCT is expected to fulfill the durability information requirements of the WAPS. Since the MCC-1 test and PCT are standard tests used to evaluate the durability of waste glasses, the leaching behavior of the HWVP glasses can be compared with that of glasses developed for the Savannah River and West Valley programs.

(a) Operated by Pacific Northwest Laboratory, Richland, Washington.

4.0 TECHNICAL APPROACH

Glass and melt properties, including viscosity, electrical conductivity, transition temperature, thermal expansion, phase behavior, and durability, were measured over a wide range of compositions selected using statistical experimental design techniques. All testing was conducted with simulated, nonradioactive glasses. The experimental data were used to develop property models as functions of composition. The models generated in this study will be used to formulate radioactive glasses, the properties of which will be determined and compared with their simulated counterparts.

A statistically-based approach was used to study the effects of composition changes on glass properties (Chick and Piepel 1984; Piepel et al. 1989). This methodology entails six basic steps: composition region definition, selection of test compositions, measurement of glass and melt properties, empirical modeling, model validation, and evaluation of component effects plots. These steps are discussed in the following sections.

4.1 COMPOSITION REGION DEFINITION

Defining the composition region to be studied during CVS-I involved selecting the components that would be varied and specifying constraints on composition. Several iterations were required to specify the component constraints. These aspects are discussed in the following sections.

4.1.1 Glass Components

The number of melts required to fit second-order mixture models to property data as a function of composition increases rapidly as the number of components increases (see Table 4.1). Since the maximum practicable number of glasses to be tested in CVS-I and CVS-II was about 100, the number of components to be varied in CVS-I was restricted to 10. First-order mixture models, which do not account for component interactions and other nonlinear behavior, require a substantially smaller number of glasses. Hence, it was decided to study 10 components in the restricted CVS-I first-order study, and reduce the number of components, if possible, for CVS-II. As discussed later, it was not possible to reduce the number of components.

TABLE 4.1. Approximate Number of Test Melts Required for Second-Order Model Fitting and Evaluation as a Function of the Number of Components

<u>Number of Components</u>	<u>Number of Test Melts</u>
6	42
7	56
8	72
9	90
10	110

The nine components that were expected to most significantly affect glass properties when varied over their expected ranges were selected. These included the frit constituents (SiO_2 , B_2O_3 , Na_2O , Li_2O , CaO , and MgO) and the major waste constituents (Na_2O , CaO , MgO , Fe_2O_3 , Al_2O_3 , and ZrO_2 - see Tables 4.2 and 4.3). Hence, SiO_2 , B_2O_3 , Na_2O , Li_2O , CaO , MgO , Fe_2O_3 , Al_2O_3 , and ZrO_2 were the nine components selected for study in CVS-I.

All other waste constituents were treated as a single tenth component called "Others." The composition of the "Others" mix (Table 4.4) was based on the nominal NCAW glass composition. As Table 4.4 indicates, the radioactive component (U_3O_8), a highly toxic component (BeO), and some rare earth components (Eu_2O_3 and Pm_2O_3) were replaced by Nd_2O_3 or MgO . Substitutions were made on a molar basis. Some minor components (≤ 0.1 wt% in the waste) and technetium were deleted from the substituted waste. The deleted components comprised 0.88 wt% of the glass.

The last column of Table 4.4 shows that the maximum amount of "Others" is most limited by SO_3 . The amount of sulfate in the nominal NCAW'87 waste is 1.8 wt%, which would limit the "Others" mix to 6.4 wt%. The sulfate was reduced to 1.1 wt% to increase the range of "Others" mix in the test glasses to 10 wt%. This change in the SO_3 concentration is expected to have no significant effect on test results.

TABLE 4.2. Oxide Compositions of NCAW'87 Waste and Substitute Waste for CVS-I

Oxide	NCAW'87 Waste (wt% oxide)	Substitute Waste (wt% oxide)	Oxide	NCAW'87 Waste (wt% oxide)	Substitute Waste (wt% oxide)
SiO ₂	4.00	4.11	PuO ₂	0.02	DEL
B ₂ O ₃	0.10	0.10	SnO ₂	0.04	DEL
Na ₂ O	17.5	18.0	Ag ₂ O	0.01	DEL
CaO	0.30	0.31	Gd ₂ O ₃	0.01	DEL
MgO	0.20	0.37	Nb ₂ O ₅	0.01	DEL
Fe ₂ O ₃	28.0	28.8	Pm ₂ O ₃	0.10	SUB Nd
ZrO ₂	15.0	15.4	Ta ₂ O ₅	0.03	DEL
Al ₂ O ₃	9.0	9.3	TiO ₂	0.01	DEL
NiO	2.30	2.36			
La ₂ O ₃	2.50	2.57		100.0	100.0
Nd ₂ O ₃	2.00	5.07			
SO ₃	1.80	1.85			
F	1.20	1.23			
MoO ₃	1.20	1.23			
U ₃ O ₈	4.70	SUB Nd			
CeO ₂	0.60	0.62			
Cs ₂ O	0.60	0.62			
CuO	0.60	0.62			
MnO ₂	0.60	0.62			
RuO ₂	0.60	0.62			
Cr ₂ O ₃	0.50	0.51			
BaO	0.40	0.41			
Pr ₆ O ₁₁	0.40	0.41			
SrO	0.40	0.41			
Tc ₂ O ₇	0.40	DEL			
PdO	0.20	0.21			
Rb ₂ O	0.20	0.21			
Rh ₂ O ₃	0.20	0.21			
Sm ₂ O ₃	0.20	0.21			
Y ₂ O ₃	0.20	0.21			
BeO	0.10	SUB Mg			
NpO ₂	0.10	DEL			
TeO ₂	0.10	DEL			
K ₂ O	0.05	DEL			
PbO ₂	0.05	DEL			
SeO ₂	0.03	DEL			
Am ₂ O ₃	0.02	DEL			
CdO	3.00	3.08			
Eu ₂ O ₃	0.02	SUB Nd			
P ₂ O ₅	0.40	0.41			

TABLE 4.3. Preliminary Compositions for NCRW, PFP, and CC Wastes Compared to NCAW (Kruger et al. 1990)

Nonvolatile Oxide	Wt% of Total Nonvolatile Oxides in HWVP Feed Streams			
	NCAW	CC	PFP	NCRW
Al ₂ O ₃	9.0	7.1	15.1	26.0
CaO	0.3	1.1	9.0	0.3
CdO	3.0	--	--	--
Cr ₂ O ₃	0.5	2.7	2.0	2.0
CuO	0.6	--	--	--
F	1.2	2.3	1.8	4.3
Fe ₂ O ₃	28.2	17.2	37.0	0.4
(La, Nd) ₂ O ₃	2.9	2.1	--	0.5
MgO	0.2	3.5	8.1	0.1
MnO ₂	0.6	3.5	5.1	--
MoO ₃	1.2	--	--	--
Na ₂ O/K ₂ O	17.6	15.7	17.1	14.0
NiO	2.3	--	--	--
P ₂ O ₅	0.9	--	--	--
Noble metals	1.0	--	--	0.2
SO ₃	0.7	0.7	2.3	--
SiO ₂	4.0	43.7	--	6.3
U ₃ O ₈	4.7	--	--	1.6
ZrO ₂	15.1	--	--	42.0
Total feed oxides	94.0	99.6	97.5	98.0

NCAW = Neutralized Current Acid Waste
 CC = Complexant Concentrate
 PFP = Plutonium Finishing Plant
 NCRW = Neutralized Cladding Removal Waste

TABLE 4.4. Composition of "Others" for CVS-I

Oxide	Normalized Others (wt%)	Substitute Others (wt%)	Critical Limits in Glass (wt%)	Maximum Others Allowed in Glass (wt%)
NiO	9.13	10.30		
La ₂ O ₃	9.92	11.19		
Nd ₂ O ₃	7.94	22.09		
SO ₃	4.37	4.93	0.50	10.15
F	4.76	5.37	1.70	31.64
MoO ₃	4.76	5.37	2.00	37.22
U ₃ O ₈	18.65	SUB Nd	8.00	42.89
CeO ₂	2.38	2.69		
Cs ₂ O	2.38	2.69		
CuO	2.38	2.69		
MnO ₂	2.38	2.69	5.00	186.10
RuO ₂	2.38	2.69		
Cr ₂ O ₃	1.98	2.24	0.50	22.33
BaO	1.59	1.79		
Pr ₆ O ₁₁	1.59	1.79		
SrO	1.59	1.79		
Tc ₂ O ₇	1.59	DEL		
PdO	0.79	0.90		
Rb ₂ O	0.79	0.90		
Rh ₂ O ₃	0.79	0.90		
Sm ₂ O ₃	0.79	0.90		
Y ₂ O ₃	0.79	0.90		
BeO	0.40	SUB Mg		
NpO ₂	0.40	DEL		
TeO ₂	0.40	DEL		
K ₂ O	0.20	DEL		
PbO ₂	0.20	DEL		
SeO ₂	0.12	DEL		
Am ₂ O ₃	0.08	DEL		
CdO	11.90	13.43	2.50	18.61
Eu ₂ O ₃	0.08	SUB Nd		
P ₂ O ₅	1.59	1.79	1.00	55.83
PuO ₂	0.08	DEL		
SnO ₂	0.16	DEL		
Ag ₂ O	0.04	DEL		
Gd ₂ O ₃	0.04	DEL		
Nb ₂ O ₅	0.04	DEL		
Pm ₂ O ₃	0.40	SUB Nd		
Ta ₂ O ₅	0.12	DEL		
TiO ₂	0.04	DEL		
<hr/>				
	100.0	100.0		

The selection of major components was based in part on the results of variability scoping tests, which have evaluated glass components comprising approximately 92 wt% of the NCAW'84 reference waste using HWVP NCAW reference glass HW-39-2 or the earlier 1.34 wt% Cr_2O_3 version HW-39-1.

4.1.2 Component Constraints

The general strategy in selecting the composition region for study during CVS-I was to make the region as large as possible so as to include compositions with unacceptable as well as acceptable properties, but not so large as to include compositions with grossly unacceptable properties or compositions unlikely to be produced by HWVP.

Two types of constraints were used to define the composition region to be studied during CVS-I. The first type, referred to as **single-component constraints**, were specified as lower and upper limits on each of the 10 selected components. Some of the lower and upper limits were based on solubility constraints determined in earlier scoping studies, although most were based on the range of potential glasses that might be produced by HWVP. This range was determined (with assistance from WHC) using updated flowsheet projections, actual aging waste storage tank analyses, and data from the B Plant process test.

The second type of constraints used to define the CVS-I composition region, referred to as **multiple-component constraints**, were generated in an attempt to eliminate compositions that would have grossly unacceptable properties. For example, scoping tests indicated that compositions with the maximum proportions of SiO_2 , Al_2O_3 , and ZrO_2 and the minimum amounts of alkalies (Na_2O and Li_2O) produced glasses with high viscosity (melting temperature as high as 1500°C) and high liquidus temperature. Although information of this type generated several multiple-component constraints, the effort to eliminate compositions with grossly unacceptable properties was not completely successful (see Section 5.1).

The single- and multiple-component constraints defining the composition region studied in CVS-I are listed in Table 4.5. Also included in Table 4.5 are critical solubility constraints for Cr_2O_3 , F, P_2O_5 , SO_3 , and noble metal oxides, as determined from the scoping studies referenced earlier.

It is anticipated that all of the multiple-component constraints and possibly some of the single-component constraints listed in Table 4.5 will eventually be replaced by inequalities combining property models with the property restrictions listed in Table 3.1. Since the $<1050^\circ\text{C}$ limit on liquidus temperature is believed to be an important restriction, the availability of a model for liquidus temperature is of crucial importance for the completeness of the CVS. Liquidus temperature depends on composition in a complex way that requires dividing the composition region into smaller segments according to the nature of the primary crystalline phases (Babcock 1977). Hence liquidus temperature requires not one empirical model, but as many models as there are primary crystallization regions. For such a number of models, the number of experimental melts listed in Table 4.1 is likely to be insufficient. However, it may be possible to fit empirical models for the primary crystalline phase regions having sufficient data.

Pelton and Eriksson (1988) developed a method by which liquidus temperature of multicomponent mixtures can be obtained by extrapolation from functional models for binary and ternary mixtures. Since the functional models are based on empirical phase diagrams, this approach is limited by the availability of phase diagrams for binary and ternary combinations of the composition region components. Unfortunately, the required phase diagrams are not available for some key components (e.g., ZrO_2). Combination of available phase diagrams and liquidus temperature data for CVS glasses may suffice for generating approximate T_L models that can replace the less accurate multiple-component constraints. This possibility will be investigated during CVS-II.

4.1.3 Iterative Development of the Composition Region

The composition region given in Table 4.5 resulted from several iterations of a process that involved defining the region of interest via single- and multiple-component constraints, generating the extreme vertices of the region,

TABLE 4.5. Composition Region (in terms of mass fractions) Studied in CVS-I

Single-Component Constraints^(a)

	<u>HW-39-4</u>	<u>Lower Limit</u>	<u>Upper Limit</u>
SiO ₂	0.5353	0.42	0.57
B ₂ O ₃	0.1053	0.05	0.20
Na ₂ O	0.1125	0.05	0.20
Li ₂ O	0.0375	0.01	0.07
CaO	0.0083	0.0	0.10
MgO	0.0084	0.0	0.08
Fe ₂ O ₃	0.0719	0.02	0.15
Al ₂ O ₃	0.0231	0	0.15
ZrO ₂	0.0385	0	0.13
Others	0.0592	0.01	0.10

Multiple-Component Constraints

	<u>Lower Limit</u>	<u>Upper Limit</u>
SiO ₂ / Al ₂ O ₃	3.0	--
(Na ₂ O + Li ₂ O)/(SiO ₂ + Al ₂ O ₃ + ZrO ₂)	0.152	0.342
MgO + CaO	--	0.10
Fe ₂ O ₃ + Al ₂ O ₃ + ZrO ₂ + Others	--	0.24
Al ₂ O ₃ + ZrO ₂	--	0.16

Critical Solubility Constraints

$$\text{Cr}_2\text{O}_3 \leq 0.005$$

$$\text{F} \leq 0.017$$

$$\text{P}_2\text{O}_5 \leq 0.010$$

$$\text{SO}_3 \leq 0.005$$

$$\text{Rh}_2\text{O}_3, \text{PdO}, \text{ and } \text{Ru}_2\text{O}_3 \leq 0.025$$

(a) An implicit constraint on the components is that their mass fractions must sum to 1.0.

experimentally testing one or more "questionable" vertex compositions, and observing the melting behavior and optical quality of the quenched glass. If any of the questionable compositions were not viable, changes were made in the CVS-I constraints and the process begun again by generating the new set of extreme vertices.

The initial composition regions considered had a higher ZrO_2 upper limit and a higher value of $\text{Fe}_2\text{O}_3 + \text{Al}_2\text{O}_3 + \text{ZrO}_2 + \text{Others}$ than the region defined in Table 4.5. Compositions with high values of ZrO_2 and $\text{Fe}_2\text{O}_3 + \text{Al}_2\text{O}_3 + \text{ZrO}_2 + \text{Others}$ exhibited excessive amounts of undissolved ZrO_2 , excessive amounts of crystalline material, or melting temperatures above 1400°C . Such results indicate that the ZrO_2 content was above its solubility limit, which was significantly affected by the concentration of Al_2O_3 in the glass. The upper limit of ZrO_2 in the glass was set to 13 wt%, the maximum sum of $\text{Fe}_2\text{O}_3 + \text{Al}_2\text{O}_3 + \text{ZrO}_2 + \text{Others}$ to 24 wt%, and an upper limit of 16 wt% for $\text{Al}_2\text{O}_3 + \text{ZrO}_2$ was added (these constraints are included in Table 4.5). Four iterations of the CVS-I composition region definition were performed to eliminate unacceptable compositions and arrive at the region given in Table 4.5.

4.2 SELECTION OF TEST COMPOSITIONS

After the glass components to be studied were identified (Section 4.1.1) and the composition region defined (Section 4.1.2), the candidate test points were generated and the test matrix selected.

4.2.1 Test Matrix Generation

The test matrix for a first-order mixture study over a constrained composition region typically consists of a subset of the extreme vertices of the region and a composition in the center of the region. The composition region defined in Table 4.5 is a polyhedron in nine dimensions (one less than the number of components because of the restriction that the component mass fractions must sum to one). The extreme vertices are the "corner points" of the polyhedron. In an extreme vertex, the component values satisfy nine constraints, where constraints may be single-component lower or upper bounds, or multiple-component constraints.

The 1820 extreme vertices of the CVS-I composition region defined by the single- and multiple-component constraints in Table 4.5 were generated using the CONVRT software (Piepel 1988). The Algorithms for the Construction of Experimental Designs (ACED) software (Welch 1987) was then used to select a subset of 17 of the extreme vertices for inclusion in the test matrix. This computer-aided experimental design approach provided an even coverage of the extreme boundary of the composition region and good support for fitting first-order mixture models. Software control procedures were followed and the appropriate paperwork completed.

In addition to the seventeen extreme vertices selected as described above, the CVS-I test matrix was completed with two interior points and four replicates. One of the interior points is the overall center point of the composition region, and the other is the HW-39-2 reference composition. Two replicates of the overall center point and single replicates of two different extreme vertex points were also included in the test matrix. The test matrix is presented and discussed in Section 4.2.2.

The test matrix includes 19 distinct compositions, while the linear mixture model only has 10 terms, so a "nine degree of freedom" estimate of model lack-of-fit can be obtained. The four replicate points provide for a "four degree of freedom" estimate of experimental error to statistically test the significance of the linear model lack-of-fit (for each property of interest). Although linear mixture models do not provide for modeling interactive behavior among the components, such information is included in the property data because the test matrix involved varying all components simultaneously.^(a) Interactive behavior among glass components is expected, and will contribute to the lack-of-fit of the linear mixture models.

(a) This is in contrast to the common, but inefficient and potentially misleading experimental strategy of varying components one-at-a-time. One-at-a-time experimentation is inefficient in that many experiments are required to learn only about individual component effects, and potentially misleading because information about interactive/nonlinear behavior of the components is not obtained.

4.2.2 First-Order CVS-I Test Matrix

The first-order CVS-I test matrix is presented in Table 4.6. Point 1 is the center point, points 2 through 18 are the extreme vertices, points 19 through 22 are the four replicates, and point 23 is the HW-39-2 composition. Appendix A contains a comparison of these test matrix target compositions to analyzed compositions of the as-melted glasses obtained by chemical analysis. Although a few differences between target and analyzed compositions were detected, they appeared to be due to analytical biases or undissolved material in some glasses. It was concluded that the target compositions best represent the compositions of the glasses tested, so they were used in all data

TABLE 4.6. Matrix of Test Compositions for CVS-I. All values are mass fractions (wt%/100).

(a) Pt	Run Order	SiO ₂	B ₂ O ₃	Na ₂ O	Li ₂ O	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	ZrO ₂	Others	Batch ^(b)
1	4	0.4801	0.1142	0.1003	0.0376	0.0275	0.0363	0.0568	0.0636	0.0429	0.0407	1
2	10	0.5500	0.0500	0.0500	0.0700	0.1000	0.0000	0.0200	0.1500	0.0000	0.0100	1
3	17	0.4200	0.2000	0.0500	0.0700	0.0000	0.0800	0.0200	0.1400	0.0100	0.0100	2
4	12	0.5700	0.2000	0.0900	0.0100	0.0200	0.0800	0.0200	0.0000	0.0000	0.0100	1
5	3	0.5700	0.0500	0.0700	0.0700	0.0000	0.0000	0.1500	0.0800	0.0000	0.0100	1
6	5	0.4400	0.2000	0.0500	0.0700	0.0000	0.0000	0.0200	0.0000	0.1200	0.1000	1
7	7	0.5700	0.0500	0.0964	0.0100	0.1000	0.0000	0.0336	0.0000	0.1300	0.0100	1
8	9	0.5363	0.0500	0.0837	0.0100	0.0000	0.0800	0.1500	0.0000	0.0800	0.0100	1
9	15	0.4200	0.1962	0.0538	0.0100	0.0000	0.0800	0.1400	0.0000	0.0000	0.1000	2
10	6	0.5700	0.0851	0.0949	0.0100	0.0000	0.0000	0.0200	0.1200	0.0000	0.1000	1
11	8	0.4200	0.1549	0.0751	0.0100	0.1000	0.0000	0.0200	0.1400	0.0000	0.0800	1
12	16	0.4200	0.1764	0.0736	0.0700	0.1000	0.0000	0.1500	0.0000	0.0000	0.0100	2
13	14	0.5700	0.2000	0.1862	0.0100	0.0000	0.0000	0.0200	0.0038	0.0000	0.0100	2
14	22	0.4200	0.2000	0.1862	0.0100	0.0000	0.0000	0.0200	0.0238	0.1300	0.0100	2
15	11	0.5589	0.0500	0.1211	0.0700	0.0000	0.0800	0.0200	0.0000	0.0000	0.1000	1
16	2	0.4327	0.0500	0.1873	0.0100	0.0000	0.0800	0.0858	0.1442	0.0000	0.0100	1
17	19	0.4545	0.0500	0.1455	0.0100	0.1000	0.0000	0.1400	0.0000	0.0000	0.1000	2
18	18	0.4214	0.0500	0.1186	0.0700	0.0200	0.0800	0.0200	0.0000	0.1300	0.0900	2
19	13	0.4801	0.1142	0.1003	0.0376	0.0275	0.0363	0.0568	0.0636	0.0429	0.0407	2
20	21	0.4801	0.1142	0.1003	0.0376	0.0275	0.0363	0.0568	0.0636	0.0429	0.0407	2
21	1	0.5700	0.2000	0.0900	0.0100	0.0200	0.0800	0.0200	0.0000	0.0000	0.0100	1
22	20	0.5363	0.0500	0.0837	0.0100	0.0000	0.0800	0.1500	0.0000	0.0800	0.0100	2
23	23	0.5153	0.0956	0.1052	0.0375	0.0289	0.0084	0.1179	0.0456	0.0063	0.0393	2

- (a) Point 1 is the center point and points 2 through 18 are extreme vertices of the composition region (which has 1820 extreme vertices). Points 19 and 20 are replicates of point 1 (the center point), while points 21 and 22 are replicates of points 4 and 8, respectively. Point 23 is the HW-39-2 composition.
- (b) The MCC-1 and PCT leach tests were randomly divided (using the random run order) into two batches to allow testing to be conducted in an efficient manner.

analyses. Although analyzed compositions were not used, information about longer-term uncertainty in analyzed compositions based on replicate analyses of glass CVS1-19 is of interest and is reported in Appendix A.

The 23 CVS-I glasses had property measurements or tests performed in the randomized run order given in Table 4.6. Because of the large amount of work involved with the MCC-1 and PCT leach testing, half of the glasses were tested in one batch and the other half in a second batch (begun about one week later) as indicated in Table 4.6. The same two batches (grouping of glasses) were used for both MCC-1 and PCT testing, although these two tests were performed at different times.

Table 4.7 contains the pairwise Pearson correlation coefficients among the 10 CVS-I glass components and batch membership. Larger correlations indicate significant confounding that may limit the ability of empirical mixture models to correctly attribute effects of the components on the properties studied. The Pearson correlation coefficients shown in Table 4.7 take values between -1.0 and +1.0, which represent perfect negative and positive pairwise correlation, respectively. A correlation of 0.0 represents a total lack of pairwise correlation.

Four correlations are identified as statistically significant (at 90% confidence level or higher) in Table 4.7: SiO_2 with Batch, Li_2O with Na_2O , MgO with CaO , and ZrO_2 with Al_2O_3 . The latter three are attributable to the multiple-component constraints used to define the region of interest, and hence were unavoidable. The significant " SiO_2 with Batch" correlation suggests that there may be some confounding of SiO_2 information in the leach test results because of performing the MCC-1 and PCT leach tests in two batches.

TABLE 4.7. Pairwise Correlations^(a) Among Glass Components^(b) and Batch Membership. Underlined values are statistically significant at the 90% confidence level.

	<u>Batch^(c)</u>	<u>SiO₂</u>	<u>B₂O₃</u>	<u>Na₂O</u>	<u>Li₂O</u>	<u>CaO</u>	<u>MgO</u>	<u>Fe₂O₃</u>	<u>Al₂O₃</u>	<u>ZrO₂</u>
SiO ₂	<u>-0.448</u>									
B ₂ O ₃	0.210	-0.286								
Na ₂ O	0.209	-0.033	-0.093							
Li ₂ O	0.030	-0.167	-0.093	<u>-0.410</u>						
CaO	-0.038	-0.105	-0.166	-0.169	0.034					
MgO	0.001	-0.026	-0.026	-0.061	-0.075	<u>-0.499</u>				
Fe ₂ O ₃	0.275	-0.089	-0.316	-0.119	-0.086	0.034	0.052			
Al ₂ O ₃	-0.244	-0.140	-0.142	-0.121	0.142	0.106	-0.165	-0.231		
ZrO ₂	0.093	-0.186	-0.103	0.081	0.018	-0.103	-0.023	-0.152	<u>-0.382</u>	
Others	0.013	-0.288	-0.076	-0.101	0.101	-0.002	-0.059	-0.107	-0.099	-0.005

- (a) Pearson correlation coefficients take values between -1.0 and +1.0, which represent perfect negative and positive pairwise linear correlations, respectively. A correlation of 0.0 represents a total lack of pairwise linear correlation.
- (b) Target compositions of the glasses as listed in Table 4.6 were used.
- (c) MCC-1 and PCT leach tests were each performed in two batches, which confounds any time effects with composition effects.

4.3 MEASUREMENT OF GLASS PROPERTIES

The following properties were measured or tests conducted for each glass composition:

- viscosity and electrical conductivity measurements for the melt over the temperature range from 1050 to 1150°C or wider
- determination of crystalline phases after 24-hour heat treatment at 1050°C and after simulated canister centerline cooling
- durability characterization by 28-day MCC-1 and 7-day PCT leach tests,
- the measurement of glass transition temperature and thermal expansion of solid and molten glass.

The procedures used are outlined in the following sections. The results were recorded in the designated laboratory notebooks. Liquidus temperature measurements were not planned as part of CVS-I, but will be made for each glass tested in CVS-II.

The measurement devices are listed on the HWVP Measurement and Test Equipment (M&TE) list (Appendix E), which is reviewed quarterly. To ensure that measurements are accurate, the devices were calibrated in accordance with

QA procedures. The viscometer and electrical conductivity unit were calibrated with NBS-711 glass every three months or if any changes occurred in the equipment. The thermocouples and temperature readouts were calibrated according to the timetable in the M&TE list.

4.3.1 Glass Fabrication

The test glasses were batched and melted according to a standard procedure. The nine major glass components varied in CVS-I (using the mass fractions listed in Table 4.6) were batched separately as oxides or inorganic salts (carbonates or nitrates). The remaining components were batched together in the proportions corresponding to the NCAW'87 waste (Table 4.2) and treated as a single component "Others" (see Table 4.4).

A quantity of 500 g of each test matrix glass was melted in platinum crucibles in air using an electrically-heated resistance furnace. The amount of glass was enough for the measurements of viscosity and electrical conductivity (150 g), glass transition temperature (50 g), and durability (100 g). At least 100 g of glass and all scrap from viscosity and electrical conductivity testing was archived under conditions specified by the applicable DOE/RW-0214 (U.S. DOE 1990) procedure. Molten glass was poured in bars and annealed for durability tests, glass transition temperature measurement, and archive purposes. The remaining glass was poured on a steel plate and air quenched. Samples of all glasses (3 to 4 g taken from different portions of melt) were sent for elemental analysis by inductively coupled plasma atomic emission spectroscopy (ICP) to confirm the batched composition.

4.3.2 Viscosity

Viscosity was measured by a rotating spindle technique and evaluated using standard viscosity measurement procedures. The glass was heated in a platinum crucible to the upper temperature to be measured ($\sim 1200^{\circ}\text{C}$) and maintained for 30 minutes. Two viscosity measurements were taken 30 minutes apart (to assess the melt stability) at successively lower temperatures until the viscosity of the melt exceeded the upper limit of the viscometer, approximately 200 Pa·s. At some temperatures, the initial and final viscosities were

such that the time rate of change exceeded 1 kPa, which indicated crystallization. Crystallization that occurred at 1050°C or higher was confirmed on thin sections of glass by optical microscopy (see Section 4.3.4).

Viscosities at 1150°C and temperatures at $\eta = 10 \text{ Pa}\cdot\text{s}$ were obtained graphically from curves fitted to $\ln(\text{viscosity})$ vs. $1/T$ plots. These data are the basis for the viscosity models discussed in the main body of this report. An alternative viscosity approach discussed in Appendix B involves fitting the raw viscosity-at-temperature data for each glass to the Fulcher equation:

$$\ln \eta = A + B / (T - T_0) , \quad (1)$$

where A, B, and T_0 are the Fulcher equation coefficients and T is temperature.

4.3.3 Electrical Conductivity

Electrical conductivity measurements were conducted by a two-probe method following established laboratory procedures. The measurements were made at the same temperatures as viscosity measurements. Two platinum-10% gold blades were inserted into the glass and the resistance of the glass between the blades was determined by an impedance bridge.

Electrical conductivity at 1150°C was determined graphically from curves fitted to $\ln(\text{electrical conductivity})$ vs. $1/T$ plots. These data are the basis for the electrical conductivity models discussed in the main body of this report. An alternative electrical conductivity approach discussed in Appendix C involves fitting the raw conductivity-at-temperature data for each glass to the Arrhenius equation:

$$\ln \epsilon = A + B/T , \quad (2)$$

where A and B are Arrhenius coefficients for electrical conductivity, and T is temperature in K.

4.3.4 Phase Behavior

Each CVS-I glass was exposed to 1050°C for 24 hours to determine whether its liquidus temperature is above or below 1050°C (liquidus temperature measurement via gradient furnace treatment will start with CVS-II). To evaluate the type and amount of crystalline material in each glass, thin sections of the quenched glass were observed optically with transmitted light. The composition of crystalline phases was qualitatively determined by Scanning Electron Microscopy with Energy Dispersive Analysis by X-rays (SEM/EDX). The X-ray diffraction technique was used to determine the content of well-defined crystalline phases; spinels are difficult to detect by XRD because they tend to form solid solutions.

For simulated canister centerline cooling (performed instead of developing the TTT diagrams -- see Section 3.0), each CVS-I glass was first heated in high-purity alumina crucibles to 1200°C and held for 30 minutes and then cooled following the time-temperature schedule presented in Table 4.8. After the heat treatment, each glass was annealed at 500°C for 2 hours. Samples were then prepared for microscope viewing and SEM and XRD analysis.

4.3.5 Glass Transition Temperature

The Perkin-Elmer TMS-2 Thermomechanical Analyzer was used to measure the glass transition temperature. Glass monoliths (approximately 1 cm x 1 cm x 2 cm) were cut from a glass bar (scraps from MCC-1 testing), annealed at 475°C for 2 hours and furnace cooled at $\leq 1^\circ\text{C}/\text{min}$. Samples were then heated at the temperature-increase rate of $20^\circ\text{C}/\text{min}$ while measuring the change in sample length versus temperature. This test was conducted in accordance with an approved procedure for determining thermal expansion of HWVP glasses and extracting parameters from expansion data.

4.3.6 Durability

The chemical durabilities of the 23 CVS-I glasses were determined by the 28-day MCC-1 and 7-day product consistency test (PCT) leach tests. Each glass was tested in duplicate by each of the two leach tests.

TABLE 4.8. HWVP Open Canister Turntable Simulated Centerline Cooling Profile

<u>Time</u> <u>(h)</u>	<u>Temp</u> <u>(°C)</u>	<u>Time</u> <u>(h)</u>	<u>Temp</u> <u>(°C)</u>	<u>Time</u> <u>(h)</u>	<u>Temp</u> <u>(°C)</u>
1	1069	12	781	23	516
2	1069	13	752	24	499
3	1056	14	725	25	483
4	1035	15	698	26	467
5	1004	16	672	27	451
6	972	17	647	28	436
7	937	18	623	29	421
8	904	19	600	30	406
9	872	20	577	31	392
10	840	21	556	32	378
11	810	22	535	33	365

For the 28-day MCC-1 static dissolution test (MCC 1983), a monolith sample of glass was suspended within a sealed Teflon container filled with deionized water by a Teflon support grid at 90°C for 28 days. The ratio of the surface area of the sample to volume of leachant is nominally 10 m⁻¹. The concentrations of glass components in the leachate were determined by ICP analysis.

The PCT requires crushed glass of a particle size between 75 and 150 µm (-100 to +200 mesh). The glass was ground in a tungsten carbide grinding chamber and then sieved through 100 and 200 mesh stainless steel sieves. The large particles remaining on the top of the 100 mesh sieve were repeatedly crushed until all glass has passed through the 100 mesh sieve. The crushed glass was added to a teflon container filled with deionized water. The leachant volume to glass mass ratio was 10 mL/g glass. The teflon container and its contents were held (without agitation) at 90°C for seven days. Aliquots of the leachate were submitted for ICP analysis.

The teflon containers used as leach test vessels were previously baked at 200°C for one week to drive off fluorine. The heat-treated containers do not release measurable amounts of fluorine during the 28-day MCC-1 tests (Jantzen 1990). The amounts of fluorine released from containers is negligible compared to the amount of fluorine released from the glass. The leachate pH was above 8.0, and therefore no free HF was present.

The results are presented in terms of normalized elemental mass releases defined as, $R_i = m_i / (f_i A)$, where R_i is the normalized mass release of element i (g/m²), m_i is the i -th element mass in leachate (g), f_i is the i -th element mass fraction in glass,^(a) and A is the sample surface area (m²). The normalized mass release of boron or lithium, which are not involved in solid reaction products, provides a measure of the glass dissolution progress. Further insight into the glass corrosion mechanism is gained by comparison of the normalized mass releases of elements which are and are not involved in solid reaction products.

4.4 EMPIRICAL MODELING

The CVS-I test matrix (Table 4.6) was designed to support fitting linear (first-order) mixture models of the form (Cornell 1990):

$$y = \sum_{i=1}^{10} b_i x_i, \quad (3)$$

where x_i is the mass fraction of i -th oxide component, b_i is the i -th component coefficient, and y is a property value or mathematical transformation thereof. Unweighted least squares regression (Draper and Smith 1981) was used to fit linear mixture models of the form (3) for each of the properties.

The term "linear mixture model" is used because the model form (3) is linear in the component mass fractions with respect to the property (or its

(a) The i -th element mass fraction is equal to the i -th component oxide mass fraction times the element-to-oxide fraction.

mathematical transformation, if one was used). However, note that if a mathematical transformation is applied, the linear mixture model is actually a non-linear function of composition with respect to the untransformed property. The linear mixture model does not, however, provide the ability to represent interactive effects of the components on the properties. Second-order models, which have such abilities, will be employed in CVS-II.

The property transformations were selected according to a procedure described by Box and Draper (1987). The procedure is based on the premise that a given model form may yield a better fit and more adequately satisfy the least squares regression "homogeneity of variance" assumption by modeling some power transformation of the property of interest rather than the property itself. The details of the procedure are not covered here, but essentially the family of power transformations $y = z^k$ (where z is a property and y its transformation) were considered for each of the properties. Values of a "goodness of fit" statistic were plotted versus several k values for each property, and the value of k yielding the "best fit" was selected. A value of $k = 0$ corresponds to a logarithmic transformation.

Linear mixture models of the form (3), where the x_i were mole fractions, were fitted for some of the properties. While there were differences in relative magnitudes of the coefficients, the mass and mole fraction models seemed to fit the data equally well. It was decided to restrict attention to the mass fraction versions of the models.

Late in the CVS-I study, it was decided to investigate modeling viscosity and electrical conductivity data as simultaneous functions of temperature and composition. This was done by expressing the coefficients of the Fulcher (for viscosity) and Arrhenius (for electrical conductivity) equations (1) and (2) as linear functions (3) of composition, and fitting the combined models to the raw viscosity and electrical conductivity data. The results are discussed in Appendices B and C.

4.5 MODEL VALIDATION

To validate the fitted property models, additional test results for glasses (radioactive and non-radioactive) not included in the CVS-I test

matrix were used. The results of these additional tests and other previously conducted and properly documented tests (e.g. melter runs) were compared to predicted property values from the CVS generated models.

The validation data set used for this work was of limited size, but will be expanded during CVS-II to include results from HWVP scoping studies and studies performed at other sites.

4.6 COMPONENT EFFECTS

To better understand the effects of the 10 CVS-I components on the glass and melt properties and to assess whether it was possible to reduce the number of components for CVS-II, component effects plots (Piepel 1982) were produced using the fitted linear mixture models. In an effects plot for a given property, there is one "effect curve" for each component. Each effect curve displays how the property changes (as predicted by the fitted property model) as the associated component varies over its allowable range (as determined by the single- and multiple-component constraints in Table 4.5). As the concentration of the component of interest varies, the concentrations of all other components are kept in constant relative proportions. This is equivalent to adding or removing a component to or from a reference mixture.

In component effects plots, the predicted property values for a component effect curve are plotted against the differences $x_i - X$, where X is the mass fraction of the component in a selected reference mixture (which may or may not be the same as the CVS internal standard glass, HW-39-4) and x_i is the concentration of the component at various points along the effect curve. As a result, the curves for all mixture components for a given property intersect at $x_i = X$. The effects plots given later in Section 5 were produced using the EFFPLT routine in the MIXSOFT software (Piepel 1989) and the GPLOTT procedure of SAS/GRAPH (SAS 1985b). Plots based on mole as well as mass fractions were investigated. Although there were differences, mole fraction effects plots gave essentially the same conclusions as mass fraction effects plots, so it was decided to focus attention on the latter.

4.7 QUALITY ASSURANCE

All testing that generated licensing-related data described in this report was conducted under QA requirements commensurate with other licensing-related programs conducted at PNL unless specifically identified. The general requirements are described in DOE/RW-0214 (U.S. DOE 1990). The specific QA requirements applicable to this work are defined in the HWVP QA plan. Testing was conducted such that all instrument calibrations and materials were traceable, test procedures and associated training activities documented in detail, and compliance of test methods and results compared with QA requirements.

Software Control Procedures (SCPs) were followed for all statistical experimental design software used to generate the CVS-I test matrix as well as for all statistical modeling and data analysis software used to statistically analyze and model the data.

5.0 RESULTS AND DISCUSSION

5.1 GLASS PROPERTIES

Glass properties measured were: viscosity and electrical conductivity (as a function of temperature), transition temperature, thermal expansion coefficients, and glass durability (releases from 28-day MCC-1 and 7-day PCT leach tests). The glass properties and the corresponding mathematical transformations applied before linear mixture models of the form (3) were fit to the data are listed in Table 5.1. Although no quantitative data for liquidus temperature were obtained, the "above or below 1050°C" tests performed provide qualitative information about the boundary between acceptable and nonacceptable compositions. The individual properties will be addressed in the following sections.

5.1.1 Viscosity

The viscosity at temperature data are given in Appendix B. A graphical curve fitting technique was applied to the viscosity at temperature values for each glass to yield viscosity at 1150°C (η_{1150}) and T_{10} values, which are given in Table 5.2. (Other treatments of the raw viscosity data are discussed in Appendix B.) The T_{10} values ranged from a low of 849°C to a high of 1406°C. These values exceed both limits of the acceptable T_{10} range of 1050°C to 1150°C. Likewise, the 1150°C viscosity data ranged from 0.4 to 84 Pa·s,

TABLE 5.1. Property Transformations Indicated by Statistical Investigation of the CVS-I Data

<u>Property</u>	<u>Description</u>	<u>Transformation</u>
T_{10}	Temperature (°C) at which viscosity = 10 Pa·s	$1/T_{10}$
η_{1150}	Viscosity (Pa·s) at 1150°C	$\ln(\eta_{1150})$
ϵ_{1150}	Electrical conductivity (S/m) at 1150°C	$(\epsilon_{1150})^{0.5}$
T_g	Glass transition temperature (°C)	none
α_s	Thermal expansion coefficient of solid glass	none
α_m	Thermal expansion coefficient of molten glass	none
R_{Mi}	28-day MCC-1 normalized i-th element release (g/m ²)	$\ln(R_{Mi})$
R_{Pi}	7-day PCT normalized i-th element release (g/m ²)	$\ln(R_{Pi})$

TABLE 5.2. CVS-I Data for Temperature at Which Viscosity is 10 Pa·s, Viscosity at 1150°C, and Electrical Conductivity at 1150°C

<u>Glass</u>	<u>T₁₀</u> <u>(°C)</u>	<u>η₁₁₅₀</u> <u>(Pa·s)</u>	<u>ε₁₁₅₀</u> <u>(S/m)</u>
CVS1-1	1088	5.8	18.7
CVS1-2	1180	13.6	26.0
CVS1-3	1002	2.4	35.6
CVS1-4	1138	8.8	9.1
CVS1-5	1172	13.2	33.5
CVS1-6	1003	2.0	47.4
CVS1-7	1306	75.2	6.9
CVS1-8	1257	36.2	8.8
CVS1-9	1106	4.0	8.4
CVS1-10	1406	83.5	20.6
CVS1-11	1187	14.5	7.5
CVS1-12	849	0.4	65.9
CVS1-13	1044	3.4	34.2
CVS1-14	1053	3.4	35.0
CVS1-15	990	2.5	58.2
CVS1-16	1204	18.0	26.4
CVS1-17	1008	2.2	28.6
CVS1-18	960	1.5	65.7
CVS1-19	1087	5.7	24.3
CVS1-20	1083	5.5	26.9
CVS1-21	1141	9.5	8.1
CVS1-22	1259	36.0	9.2
CVS1-23	1079	5.6	28.1

greatly exceeding the acceptability limits of 2 to 10 Pa·s (Table 3.1). This indicates that the region tested is considerably larger in some directions than the region of acceptable compositions. Viscosities of four glasses, namely #7, 8, 10, and 22 (which is a replicate of 8), were too high at 1050°C (greater than 100 Pa·s) to be measurable with the rotating spindle technique. These glasses are high in SiO₂ and low in B₂O₃ and Li₂O.

Several glasses exhibited time-dependence of viscosity at lower temperatures: #3 (<900°C), 4 (<1000°C), 5 (<1000°C), 8 and 22 (<1200°C), 9 (<1100°C), 11 (<1100°C), 15 (<900°C), and 16 (<1100°C). Crystallization tests, which were performed for temperatures 1050 and 1150°C, showed that the viscosity time-dependence of glasses #8 (and 22), 9, and 16 was caused by crystallization. Not all crystalline phases had the same effect. Precipitation of large elongated randomly-oriented crystals caused viscosity to change rapidly: this

was the case for MgSiO_3 in glasses #8 (and 22) and 16, and the as yet unidentified compound in glass #9. However, large crystals of $\text{CaZr}(\text{SiO}_4)_3$ in glass #7 did not lead to time-dependent viscosity. Small scattered crystals of spinel had no detectable effect on viscosity (#5 and 10). Viscosity of glasses #5 and 11 decreased with time. No crystallinity was detected in glass #11 at 1050°C , at which temperature the decrease of viscosity with time was noticed. This result is difficult to understand, but no attempt was made to confirm it by repeating the test. For other glasses (#3, 4, 8, 9, 15, 16, and 22) viscosity increased with time.

The linear mixture model (3) was fitted to natural log transformed values of viscosity at 1150°C and reciprocal transformed values of T_{10} , as contained in Table 5.2. The coefficients of the linear model are given later in Table 5.9. The component effects plots (as discussed in Section 4.6) with respect to the HW-39-4 reference glass were produced using the η_{1150} and T_{10} fitted linear mixture models, and are displayed in Figures 5.1 and 5.2, respectively. Figure 5.1 illustrates that viscosity of the HW-39-4 reference glass is increased most (in order) by $\text{SiO}_2 > \text{Al}_2\text{O}_3 > \text{ZrO}_2$, and decreased most (in order) by $\text{Li}_2\text{O} < \text{Na}_2\text{O} < \text{B}_2\text{O}_3$. That is, SiO_2 increases viscosity the most while Li_2O decreases viscosity the most. The components CaO , MgO , Fe_2O_3 , and Others appear to have mild reducing effects on viscosity, although due to the uncertainties in the fitted models they could have negligible or even mild increasing effects. The results in Figure 5.2 for T_{10} are similar to those for η_{1150} , except that the reducing effect of CaO on T_{10} is more pronounced.

5.1.2 Electrical Conductivity

The electrical conductivity at temperature data are given in Appendix C. A graphical curve fitting technique was applied to the electrical conductivity at temperature values for each glass to yield electrical conductivity at 1150°C (ϵ_{1150}) values, which are summarized in Table 5.2. (Other treatments of the raw electrical conductivity data are discussed in Appendix C.) Values of ϵ_{1150} ranged from 2.9 to 65.9 S/m, which exceed both limits of the acceptable electrical conductivity range of 18 to 50 S/m. Electrical conductivity was not detectably affected by crystallization.

FIGURE 5.1. Predicted Component Effects on Viscosity at 1150°C Relative to the HW-39-4 Composition

FIGURE 5.2. Predicted Component Effects on Temperature at Which Viscosity is 10 Pa·s Relative to the HW-39-4 Composition

The linear mixture model (3) was fitted by least squares (the REG procedure in SAS 1985a) to the ϵ_{1150} data (which had first been transformed by the square root transformation). The linear mixture model coefficients are given later in Table 5.8. The component effects plot given in Figure 5.3 shows that electrical conductivity of the HW-39-4 reference glass is increased by the two alkali oxide components in the order (based on mass fraction) $\text{Li}_2\text{O} > \text{Na}_2\text{O}$. Electrical conductivity is reduced most by the components in the order $\text{SiO}_2 < \text{MgO} < \text{Al}_2\text{O}_3 < \text{CaO} < \text{ZrO}_2$. Except for SiO_2 , the effects of these components are mild. The remaining components, Fe_2O_3 , B_2O_3 , and Others, have essentially negligible effects.

All CVS-I glasses (except one) with ϵ_{1150} values beyond the limits of acceptability were also beyond the limits of acceptability for viscosity or durability. This indicates that, as a rule of thumb, glasses with acceptable viscosity and durability are likely to have acceptable electrical conductivity.

5.1.3 Glass Transition Temperature

Glass transition temperature (T_g) values for CVS-I glasses are summarized in Table 5.3, and range from 429 to 579°C. A linear mixture model of the form (3) was fitted to the data (untransformed). The linear mixture model coefficients are given later in Table 5.8.

The component effects plot given in Figure 5.4 shows that transition temperatures are strongly reduced by Li_2O , and to a lesser extent by Na_2O . SiO_2 and ZrO_2 significantly increase T_g . All other components have moderate to negligible effects.

5.1.4 Thermal Expansion Coefficients

The thermal expansion coefficient data for solid and molten glass are included in Table 5.3. Linear mixture models of the form (3) were fitted to the data (untransformed), and the model coefficients are given later in Table 5.8. The component effects plots produced from the fitted models are given in Figures 5.5 and 5.6. Alkali oxides (Li_2O more than Na_2O) increase and SiO_2 decreases thermal expansion. Al_2O_3 , ZrO_2 , and MgO increase the

TABLE 5.3. CVS-I Data for Glass Transition Temperature, Thermal Expansion Coefficient for Solid Glass, Thermal Expansion Coefficient for Molten Glass, and Liquidus Temperature

Glass Sample	T_g (°C)	$\alpha_s^{(a)}$ ($10^{-6}/K$)	$\alpha_m^{(b)}$ ($10^{-6}/K$)	Liquidus < 1050°C
CVS1-1	486.2	8.9	103.0	yes
CVS1-2	487.6	9.4	72.0	yes
CVS1-3	486.3	9.2	111.3	yes
CVS1-4	524.6	6.9	69.7	yes
CVS1-5	450.9	9.1	103.5	yes
CVS1-6	490.5	8.6	96.5	no
CVS1-7	579.1	8.0	60.7	no
CVS1-8	547.0	8.1	79.8	no
CVS1-9	516.9	6.6	82.8	no
CVS1-10	519.4	6.6	53.7	no
CVS1-11	537.1	8.5	57.1	yes
CVS1-12	469.3	10.3	132.3	yes
CVS1-13	526.7	10.0	120.4	yes
CVS1-14	520.4	9.4	95.1	yes
CVS1-15	429.6	10.6	96.1	yes
CVS1-16	488.5	10.9	58.6	no
CVS1-17	490.4	11.1	117.8	yes
CVS1-18	429.3	12.4	75.7	no
CVS1-19(c)	491.3	8.3	87.8	yes
CVS1-20(c)	496.3	9.5	91.6	yes
CVS1-21(c)	543.5	5.6	101.0	yes
CVS1-22(c)	559.9	7.1	49.2	no
CVS1-23	486.5	9.1	123.0	yes

-
- (a) Coefficient of thermal expansion for solid glass.
(b) Coefficient of thermal expansion for molten glass.
(c) CVS1-19 and CVS1-20 are replicates of CVS1-1. CVS1-21 and CVS1-22 are replicates of CVS1-4 and CVS1-8, respectively.

FIGURE 5.4. Predicted Component Effects on Glass Transition Temperature Relative to the HW-39-4 Composition

FIGURE 5.5. Predicted Component Effects on Thermal Expansion Coefficient for Solid Glass Relative to the HW-39-4 Composition

FIGURE 5.6. Predicted Component Effects on Thermal Expansion Coefficient for Molten Glass Relative to the HW-39-4 Composition

thermal expansion of molten glasses even more than SiO_2 , but these oxides have little effect on the thermal expansion of solid glass. The remaining components have moderate to negligible effects.

5.1.5 Glass Crystallization

In CVS-I, it was only determined whether the liquidus temperature was above or below 1050°C . The pass/fail criterion was based on XRD detection of a crystalline material, with a detection limit of approximately 1-2% crystallinity. The pass/fail data for the CVS-I glasses are included in Table 5.3. A logistic transformation was applied to the pass/fail data and a linear mixture model of the form () fitted, but the goodness of fit was suspect due to the small data set. Typically, much larger data sets are required to adequately model pass/fail type data. Hence, the modeling results are not presented.

Table 5.4 contains a summary of the crystalline phases detected by XRD for both heat treatments (24 hours at 1050°C and simulated canister centerline cooling) of the CVS-I glasses.

Of the 19 distinct CVS-I glasses (17 vertices, 1 centroid, and 1 reference) heat treated at 1050°C for 24 hours, crystals were found in glasses 6 through 10, 16, and 18, and no crystals or less than 1% crystals were detected in glasses 1 through 5, 11 through 15, and 17. The results for the replicate glasses [#19 and 20 (replicate of #1), #21 (replicate of #4), and #22 (replicate of #8)] were similar to the results for the glasses they replicated, and are not specifically addressed in this discussion. The major phases detected were MgSiO_3 , $\text{Ca}_2\text{Zr}(\text{SiO}_3)_4$, ZrSiO_4 , ZrO_2 (undissolved), and various spinels (Fe_3O_4 type oxides with substitutions of Ni, Cr, and Al in the lattice positions). For all but one of the glasses that failed the liquidus criterion, the sum of the mass fractions of Fe_2O_3 , Al_2O_3 , ZrO_2 , and Others was at the maximum level allowed (24 wt%, see Table 4.6). However, if this sum was less than 24 wt%, the maximum levels of individual components (Table 4.5) did not necessarily result in devitrification at $T \geq 1050^\circ\text{C}$.

TABLE 5.4. X-Ray Diffraction Analysis of CVS-I Heat Treated Glasses

Glass	24 Hours at 1050°C		Sim. Canister Centerline Cooling	
	Phase	wt%	Phase	wt%
CVS1-1	None	0	NaFeSi ₂ O ₆	6-8
CVS1-2	?	<1	?	<1
CVS1-3	?	<1	Mg ₂ SiO ₄	<1
CVS1-4	?	<1	?	<1
CVS1-5	None	0	Spinel	3-5
			Li ₂ SiO ₃	1
			?	<1
CVS1-6	ZrSiO ₄	5-7	ZrSiO ₄	8-10
			ZrO ₂	<1
CVS1-7	CaZr(SiO ₃) ₄	4-6	CaZr(SiO ₃) ₄	3-5
CVS1-8	ZrSiO ₄	12-15	ZrSiO ₄	10-12
	MgSiO ₃	3-4	MgSiO ₃	2-4
			NaFeSi ₂ O ₆	3-5
CVS1-9	?	4-6	?	5-7
CVS1-10	Spinel	1-2	Spinel	1-2
CVS1-11	?	<1	None	0
CVS1-12	None	0	?	<1
CVS1-13	?	1	None	0
CVS1-14	None	0	None	0
CVS1-15	?	<1	Li ₂ SiO ₃	2-3
CVS1-16	Spinel	1-2	NaAlSiO ₄	15-18
	MgSiO ₃	<1		
CVS1-17	None	0	?	<1
CVS1-18	ZrO ₂	8-10	ZrO ₂	12-13
			Li ₂ SiO ₃	2-3
CVS1-19	None	0	NaFeSi ₂ O ₆	8-10
CVS1-20	None	0	NaFeSi ₂ O ₆	8-10
CVS1-21	?	<1	?	<1
CVS1-22	ZrSiO ₄	12-15	ZrSiO ₄	10-12
	MgSiO ₃	3-4	MgSiO ₃	2-4
			NaFeSi ₂ O ₆	2-3
CVS1-23	None	0	NaFeSi ₂ O ₆	2-3

? = Unidentified.

CVS-I glasses can be divided into five groups according to the major component (other than silica) that enters the primary crystalline phase:

- high zirconia glasses
- high iron glasses
- high magnesia glasses
- high calcium glasses
- other glasses.

Within each group, the concentration of the second and third major component determines whether crystals precipitate and their composition. The first three groups overlap, because some glasses may be rich in both zirconia and iron (#8), magnesia and iron (#16), or zirconia and magnesia (#8).

High zirconia glasses were #6-8, 14, and 18. No crystals were detected in glass #14, which was rich in boron oxide (20 wt%) and alkali oxides (18 wt% Na_2O and 1 wt% Li_2O). Glass #18, which has high alkali (12 wt% Na_2O and 7 wt% Li_2O), high magnesia (8 wt%), and low silica (42 wt%) contents, contained undissolved zirconia (ZrO_2). In glass #8 (8 wt% Na_2O , 1 wt% Li_2O , 8 wt% MgO , and 54 wt% SiO_2), two crystalline phases were found: zircon (ZrSiO_4) and enstatite (MgSiO_3). Zircon was detected also in #6, whereas in #7, which was rich in calcium oxide (10 wt%), a massive crystallization of $\text{Ca}_2\text{ZrSi}_4\text{O}_{12}$ occurred. Unmolten zirconia and precipitated zircon sedimented to the crucible bottom. One can conclude that high zirconia glasses should contain minimum alkali earth oxides (CaO , MgO). High boron oxide concentration combined with high alkali oxide content prevents precipitation of crystalline phases, but the glass has low durability (#14).

Six glasses can be classified as high iron (#5, 8, 9, 12, 16, and 17). Spinel precipitated in glass #16, at temperatures as high as 1150°C. Spinel was also found in glass #10, which has low iron oxide content (2 wt%) and high Others content (10 wt%). The amount of spinel was dependent on the content of NiO and Cr_2O_3 (present as a part of Others). Increased precipitation of spinel was found near crucible walls, where the glass was enriched with alumina.

High magnesia glasses (#3, 4, 8, 9, 15, 16, and 18) produced enstatite (MgSiO_3) only in two cases (#8 and 16). High lime glasses (#2, 7, 11, 12, and 17) precipitated calcium-containing crystals only in one case (#7).

Samples given the simulated canister centerline cooling treatment exhibited the same crystalline phases as the samples held at 1050°C and quenched, as well as additional phases (acmite, nepheline, and lithium metasilicate) that precipitated at temperatures lower than 1050°C. Acmite [$\text{NaFe}(\text{SiO}_3)_2$] was found in glasses #1 (the centroid glass), 8, 23 (the HW-39-2 glass), and their replicates. Traces of acmite were seen by optical microscope in glass #17. Nepheline (NaAlSiO_4) precipitated in glass #16 and lithium metasilicate (Li_2SiO_3) in glasses #5, 15, and 18. In some glasses (#2, 4, 5, 12, and 17), traces of unidentified crystalline phases were detected by XRD. No crystalline phases were detected in glasses #11, 13, and 14.

Interestingly, acmite crystallizes in the central region of the composition range tested (glasses #1 and #23), but was found in only two vertex glasses, both of them combining high iron (>14 wt% Fe_2O_3) and high sodium (>8 wt% Na_2O) content. The only other glass possessing such a combination (#16, 8.6 wt% Fe_2O_3 and 18.7 wt% Na_2O) precipitated nepheline, most likely because of its high aluminum content (14.4 wt.% Al_2O_3). Five other high alumina glasses had a significantly lower content of sodium oxide (<10 wt%) than glass #16; no nepheline was detected in these glasses. Seven glasses had higher lithium content (7 wt% Li_2O), but crystals of lithium silicate were detected only in three of these glasses, all with low B_2O_3 content (5 wt%) and Na_2O content at least 7 wt%. These observations may be used as guidance for judging computer-generated test compositions.

5.1.6 Glass Durability

The Si, B, Li, Na, Mo, and Cs elemental releases and uncertainties from duplicate 28-day MCC-1 and 7-day PCT leach tests of the CVS-I glasses are contained in Appendix D. Normalized B release seems to provide the best estimate of the extent of glass dissolution for the following reasons: 1) all B from glass enters into the leachate (does not precipitate in the gel layer), 2) B is released exclusively by dissolution of the glass network (not by a diffusion process), 3) B_2O_3 is present in CVS glasses in a sufficiently high

concentration, and 4) B concentration in the leachate is determined by ICP with satisfactory precision.

5.1.6.1 28-Day MCC-1 Data and Discussion

The Si, B, Li, Na, Mo, and Cs release values averaged over duplicate 28-day MCC-1 test results are contained in Table 5.5. The averaged B releases ranged from roughly 3 to 700 g/m². The CVS-I glasses can be classified into two groups based on the normalized B release values:

Group A. Low-to-moderate normalized B release (≤ 75 g/m²)

Group B. High normalized B release (> 115 g/m²)

Group B contains glasses #4, 6, 9, 12, 13, 15, and 21, while Group A contains the other glasses.

All glasses with high B₂O₃ mass fraction (> 0.17) and low Al₂O₃ mass fraction (< 0.02), and one glass with low B₂O₃ mass fraction (0.05), form Group B. The glass (#15) with high normalized B release and low B₂O₃ fraction contained neither Al₂O₃ nor ZrO₂. Glasses with low B₂O₃ mass fraction, no Al₂O₃, and high ZrO₂ mass fraction (0.08 to 0.13) exhibited a low extent of dissolution. All glasses with high Al₂O₃ mass fraction (≥ 0.06) exhibit low normalized release, including those with high mass fraction of B₂O₃ (0.20). These results suggest the following:

- Glasses with high Al₂O₃ content dissolve relatively slowly regardless of B₂O₃ content.
- Glasses with moderate B₂O₃ content and high ZrO₂ content dissolve relatively slowly even if they contain no Al₂O₃.
- Glasses with high B₂O₃ content and low Al₂O₃ content dissolve relatively rapidly regardless of ZrO₂ content.

For glasses with a relatively high extent of dissolution (Group B), the normalized B and Li release values were almost equal, whereas for the glasses of Group A, the Li/B release ratio was 1.1 to 1.2. The difference between the normalized releases of Li and B may be attributable to alkali ion extraction,^(a) which occurs simultaneously with glass dissolution and releases additional alkali ions at the beginning of the process (Pederson et al. 1986).

(a) D. M. Strachan, private communication (1990).

TABLE 5.5. Si, B, Li, Na, Mo, and Cs Normalized Releases and Leachate pHs Averaged Over Duplicate 28-day MCC-1 Leach Tests of the CVS-I Glasses

Glass	28-Day MCC-1 Normalized Release (g/m ²) ^(a)						pH
	Si	B	Li	Mo	Na	Cs	
CVS1-1	8.99	12.47	11.95	12.24	12.36	9.68	9.95
CVS1-2	6.82	7.46	7.19	8.24	7.41	8.48	10.04
CVS1-3	10.84	15.57	15.56	15.50	15.62	10.25	9.58
CVS1-4	64.85	189.71	161.94	177.29	180.44	102.50	9.65
CVS1-5	10.42	11.48	10.46	11.59	10.83	14.00	10.06
CVS1-6	45.38	121.30	108.60	118.38	92.99	9.86	9.91
CVS1-7	7.50	11.00	10.50	11.31	10.75	10.25	9.85
CVS1-8	11.73	17.88	16.73	18.29	17.31	15.57	9.72
CVS1-9	45.79	158.72	148.82	124.10	150.30	69.38	9.24
CVS1-10	2.70	2.74	3.33	2.37	2.80	2.38	8.51
CVS1-11	6.77	8.25	8.17	7.83	8.32	5.92	9.16
CVS1-12	49.35	118.48	122.58	118.66	122.68	106.44	10.86
CVS1-13	187.62	690.51	652.69	665.87	637.30	102.50	10.59
CVS1-14	23.94	73.63	68.06	45.93	57.69	10.05	10.09
CVS1-15	73.40	210.29	172.04	199.20	172.50	57.36	12.37
CVS1-16	11.38	16.85	15.38	18.01	16.01	16.36	10.48
CVS1-17	20.24	39.10	40.86	38.11	40.85	37.06	10.96
CVS1-18	5.91	24.05	23.66	20.56	23.24	13.15	11.03
CVS1-19 ^(b)	8.95	13.02	13.18	12.29	13.05	10.17	9.88
CVS1-20 ^(b)	8.84	12.50	12.50	11.91	12.49	9.20	9.88
CVS1-21 ^(b)	61.10	205.79	177.74	194.04	192.42	102.50	9.65
CVS1-22 ^(b)	11.61	17.36	17.10	17.45	16.99	15.77	9.76
CVS1-23 ^(c)	12.02	15.37	15.71	14.64	15.63	14.00	9.96

- (a) Release rates were normalized using the target compositions given in Table 4.6.
- (b) CVS1-19 and CVS1-20 are replicates of CVS1-1. CVS1-21 and CVS1-22 are replicates of CVS1-4 and CVS1-8, respectively.
- (c) The result from one of two duplicate tests--the other was obviously erroneous.

The present data indicate that the relative difference between Li and B normalized releases decreases as the total extent of dissolution increases.

This is in agreement with the view that the absolute difference between Li and B releases is generated at the beginning of the process and does not change as dissolution progresses. A typical value for this difference is $R_{Li} - R_B = 1 \text{ g/m}^2$. This corresponds to the equivalent lithium-depleted depth of $\delta = (R_{Li} - R_B)/\rho = 400 \text{ nm}$, where ρ is glass density ($\rho = 2.5 \times 10^6 \text{ g/m}^3$).

The normalized release of Na is higher than (by a factor up to 1.1) or equal to the normalized B release for glasses with low extent of dissolution (Group A) and lower than (by a factor down to 0.7) or equal to the normalized B release for glasses with high extent of dissolution (Group B). A similar trend, that is, lower relative normalized release values (compared to B release) for rapidly dissolved glasses, was observed for Cs, but the scatter of data is higher than for Na or Li. For glasses that dissolve relatively quickly, the Cs/B release ratio is within the range 0.1 to 0.6, whereas for slowly dissolving glasses, it is within the range 0.7 to 1.4.

Apart from being extracted, Na and Cs ions are also partly absorbed in the alteration (gel) layer (Strachan et al. 1982). This may explain why Na and Cs normalized releases were lower than the normalized releases of B for glasses that dissolved to a greater extent: the absorption in the gel layer is expected to increase as the amount of glass dissolved grows. The higher scatter of the Cs data can be caused by the low value of the Cs_2O fraction in glass (0.1%); this low content of Cs_2O in glass makes the value of the normalized Cs release less precise.

The normalized Si release is substantially lower than that of B because the leachate quickly becomes saturated with Si. Additional Si released from the glass network is retained in the gel layer. The ratio of the normalized releases of Si and B for glasses with low to moderate extent of dissolution is 0.77, but is much lower (0.30) for glasses with relatively high dissolution rate.

The normalized Mo release is approximately the same as the normalized B release. The Mo/B ratio in terms of normalized releases is 0.9 to 1.1 on average and, similar to other elements, shows a tendency to be indirectly proportional to the extent of dissolution.

Whereas the differences between normalized releases of different elements can be satisfactorily explained by the alkali extraction and gel layer formation, the question of why Group B glasses dissolved by up to an order of magnitude more rapidly than those of Group A cannot be easily explained by the differences in composition. The difference in durability for Group A and Group B glasses is clearly a result of a severe nonlinearity of the release-composition dependence. This nonlinearity can be produced either by an abrupt change in glass structure with composition, which seems unlikely, or by phase separation.

As is well known (Tomozawa 1979), borosilicate glasses are prone to phase separation, which is suppressed by Al_2O_3 and, to a lesser extent, by ZrO_2 . The effect of phase separation on durability is well established (Tomazowa 1979, Shelby 1983). The overall durability is determined by the phase which is connected, whereas the dispersed phase has little effect. If two immiscible phases significantly differ in durability, a sharp change in durability occurs within a narrow composition region in which the dispersed phase becomes connected. This suggests that the high normalized release of Group B glasses could be caused by phase separation producing a connected B-rich phase, whereas the Group A glasses could be single phase or phase separated with the more durable phase connected and the less durable one dispersed. The low Si/B ratio in the leachates for Group B glasses could be a consequence of the reduced Si content of the B-rich phase even if the leachate is not saturated by Si. No attempt has been made to examine the glasses for phase separation by electron microscopy.

Since phase separation is sensitive to the heat treatment, one can expect that the durability of phase-separated glasses is heat-treatment sensitive. The effect of heat treatment on waste glasses was observed by Bickford and Jantzen (1984) and Jantzen and Bickford (1985). They found that crystallization produces only a minor effect on leachability of

alumina-containing glasses with up to 30 volume percent of crystalline phase (spinel and acmite). The authors concluded that devitrification affects durability less than changes in chemical composition. Phase separation was unlikely to occur in most of their glasses because of the Al_2O_3 content of 5.6 and 11.1 wt% (Bickford and Jantzen 1986). However, they tested a glass with a lower Al_2O_3 content (SRL-165 High Fe, which contained 2.2 wt% Al_2O_3 and 6.5 wt% B_2O_3) and found more than ten times higher B release after heat treatment (Jantzen and Bickford 1985). They attributed this finding to cracking caused by the thermal-expansion mismatch of the glass and crystals. The possibility that this low durability could be caused by phase separation was not considered.

More recent results at PNL confirm that there is no simple correlation between crystallization and durability. Maximum crystallinity was observed after the heat treatment of glasses at 800°C. This had a negligible effect on durability, whereas heat treatment at 600°C, which did not produce any detectable crystallinity, had a significant effect on durability. This indicates that liquid-liquid separation may be involved. The MCC-1 data by Bickford and Jantzen (1984) and Jantzen and Bickford (1985) exhibit a larger scatter than MCC-3 data, which is probably caused by the inhomogeneous stress within partly crystallized MCC-1 monoliths.

5.1.6.2 MCC-1 Linear Mixture Models and Effects

The linear mixture model (3) was fitted to the B, Li, Na, Mo, Cs, and Si averaged MCC-1 normalized release values listed in Table 5.5 (after applying natural log transformations). The strongly nonlinear dependence of release (log transformed) on composition necessitated refitting the linear mixture model after deleting the data points corresponding to glasses 4, 6, 9, 13, 15, and 21 (which had the six highest B releases). Glass 12 had moderately high B release similar to that of #6, but it agreed well with fitted models and so it was not deleted. The model coefficients for both the full and reduced sets of data are given later in Tables 5.11 and 5.12.

The component effects plots for the linear mixture models fitted to MCC-1 normalized B releases for the full and reduced sets of data are given in Figures 5.7 and 5.8, respectively. For the full set of glasses, Li_2O

FIGURE 5.7. Predicted Component Effects on MCC-1 Normalized B Release
(Based on Linear Mixture Model Fitted to Full Data Set)
Relative to the HW-39-4 Composition

FIGURE 5.8. Predicted Component Effects on MCC-1 Normalized B Release (Based on Linear Mixture Model Fitted to Reduced Data Set) Relative to the HW-39-4 Composition

increases B release the most, followed closely by Na_2O and B_2O_3 . MgO may also increase B release, but this is less clear due to uncertainty in the fitted linear mixture model. Al_2O_3 decreased B release the most, followed by ZrO_2 with a somewhat smaller effect. Fe_2O_3 , Ca , SiO_2 , and Others appear to reduce the B release, but the uncertainty in the fitted model is such that these components may not affect, or even mildly increase, B release.

For the reduced set of glasses, the component effects on B release are somewhat different. Li_2O and Na_2O increase B release the most, followed by Fe_2O_3 , B_2O_3 , and CaO . SiO_2 is the only component that significantly decreases B release. The remaining components (ZrO_2 , MgO , Al_2O_3 , and Others) have mild to negligible effects.

5.1.6.3 PCT Results

The Si, B, Li, Na, Mo, and Cs release values averaged over duplicate 7-day PCT results are contained in Table 5.6. The PCT averaged normalized B releases ranged from roughly 0.07 to 21 g/m^2 . The averaged normalized B releases from the 7-day PCT and 28-day MCC-1 tests are plotted versus one another in Figures 5.9 and 5.10. The untransformed releases are plotted in Figure 5.9, while the natural log transformed releases are plotted in Figure 5.10. Several "outlying" points are identified in each figure. Glass #13 has a much larger MCC-1 to PCT release ratio than do the other glasses (Figure 5.9), although it does not appear as different on the log-log plot (Figure 5.10). Plots similar to Figures 5.9 and 5.10 but with various outlying glasses deleted were completed, but are not shown here. Based on all such plots, glasses 13, 14, and 18 were selected for repeat leach testing by the MCC-1 and PCT tests to verify the results. The results from the repeat MCC-1 and PCT leach tests are given in Table 5.7, and are seen for the most part to be comparable to the results from the first tests.

Linear mixture models of the form (3) were fitted to the averaged Si, B, Li, Na, Mo, and Cs elemental PCT releases for all CVS-I data. The model coefficients are given later in Table 5.11. Linear mixture models were also fitted to a reduced set of data obtained by deleting the data points corresponding to glasses 4, 9, 13, 15, 18, and 21 (which had the six largest B release values). However, these data points agreed fairly well with the

TABLE 5.6. Si, B, Li, Na, Mo, and Cs Normalized Releases and Leachate pHs Averaged Over Duplicate 7-day PCT Leach Tests of the CVS-I Glasses

Glass	7-Day MCC-1 Normalized Release (g/m ²) ^(a)						pH
	Si	B	Li	Mo	Na	Cs	
CVS1-1	0.167	0.521	0.529	0.439	0.403	0.056	10.92
CVS1-2 ^(c)	0.054	0.066	0.154	0.061	0.064	0.057	11.42
CVS1-3	0.172	0.864	0.791	0.468	0.580	0.042	9.85
CVS1-4	0.540	20.639	16.935	23.033	17.034	1.735	9.67
CVS1-5	0.318	0.355	0.462	0.327	0.191	0.148	11.22
CVS1-6	0.312	6.113	4.892	4.188	3.046	0.124	10.07
CVS1-7	0.114	0.287	0.331	0.304	0.339	0.143	10.91
CVS1-8	0.265	1.238	0.744	1.160	0.805	0.074	10.42
CVS1-9	0.345	10.993	8.602	7.399	7.897	0.922	8.69
CVS1-10	0.104	0.127	0.386	0.094	0.095	0.029	9.76
CVS1-11	0.041	0.099	0.187	0.066	0.099	0.057	9.99
CVS1-12	0.825	4.662	4.171	4.739	4.395	1.606	11.12
CVS1-13	0.786	14.072	12.903	13.122	12.413	1.104	10.37
CVS1-14	0.149	9.847	8.011	1.312	5.790	0.311	9.63
CVS1-15	0.967	18.778	11.198	19.125	13.995	2.799	13.03
CVS1-16	0.241	0.523	0.266	0.468	0.540	0.152	12.01
CVS1-17	0.663	2.235	2.075	2.234	2.304	0.940	11.57
CVS1-18	1.531	11.238	8.065	10.732	8.040	1.569	12.25
CVS1-19 ^(b)	0.166	0.523	0.533	0.448	0.433	0.065	10.29
CVS1-20 ^(b)	0.156	0.455	0.468	0.396	0.396	0.051	10.16
CVS1-21 ^(b)	0.459	18.850	15.591	19.543	15.536	1.744	9.68
CVS1-22 ^(b)	0.259	1.119	0.704	1.122	0.760	0.067	9.81
CVS1-23	0.229	0.525	0.535	0.487	0.487	0.063	10.29

- (a) Release rates were normalized using the target compositions given in Table 4.6.
- (b) CVS1-19 and CVS1-20 are replicates of CVS1-1. CVS1-21 and CVS1-22 are replicates of CVS1-4 and CVS1-8, respectively.
- (c) Elemental release values are from one of the two duplicate leach tests.

models fit to all of the data, and it was decided that "reduced data set models" were not required for the PCT results.

The component effects plot produced using the PCT normalized B release linear mixture model corresponding to the full data set is given in Figure 5.11. The components Li₂O, Na₂O, MgO, and B₂O₃ (in that order) increase B release, while Al₂O₃ and SiO₂ decrease PCT normalized B release. ZrO₂, Fe₂O₃,

FIGURE 5.9. Scatterplot of Normalized B Releases from 7-Day PCT and 28-Day MCC-1 Leach Tests for the CVS-I Glasses

and CaO also appear to decrease B release, but this is not clear due to uncertainty in the fitted model. The Others component appears to have a negligible effect on PCT normalized B release.

5.1.6.4 Fe(II)/Fe Ratio

The Fe(II)/Fe ratio was not specifically addressed as a variable affecting glass durability in CVS-I, since in previous work it did not exhibit a measurable effect on dissolution of HWVP glasses over the range from 0 to 0.53. The actual Fe(II)/Fe value for the CVS glasses is expected to be close to zero because iron is added as Fe_2O_3 and no reducing agents are introduced in the batches.

FIGURE 5.10. Scatterplot of Log Transformed Normalized B Releases from 7-Day PCT and 28-Day MCC-1 Leach Tests for the CVS-I Glasses

5.2 CORRELATIONS AMONG GLASS PROPERTIES

Pairwise Pearson correlation coefficients for the untransformed and transformed (Table 5.1) glass and melt properties are given in Tables 5.8 and 5.9, respectively. The purpose of investigating pairwise property correlations is to gain an understanding of the extent to which the results of varying composition for one property by are related for other properties.

In Table 5.8, the strongest pairwise correlations (0.99 and above) occur among the normalized 28-day MCC-1 releases of Si, B, Li, Mo, and Na, indicating that the results for these elements are highly linearly related. Normalized 7-day PCT releases for B, Li, Mo, and Na were also highly correlated, although not quite to the extent as for MCC-1 releases. Smaller correlations

FIGURE 5.11. Predicted Component Effects on PCT Normalized B Release
(Based on Linear Mixture Model Fitted to Full Data Set)
Relative to the HW-39-4 Composition

TABLE 5.7. Normalized Elemental Releases (Averaged Over Duplicate Leach Tests) from Repeat Tests on Three Glasses

Glass	28-Day MCC-1 Normalized Release (g/m ²) ^(a)					
	Si	B	Li	Mo	Na	Cs
CVS1-13	187.43	651.13	586.02	642.14	600.75	94.61
CVS1-14	23.48	70.58	65.59	41.88	55.62	7.29
CVS1-18	5.76	24.12	23.20	20.18	22.33	9.86

Glass	7-Day MCC-1 Normalized Release (g/m ²) ^(a)					
	Si	B	Li	Mo	Na	Cs
CVS1-13	2.343	16.077	13.978	14.448	14.476	1.676
CVS1-14	0.144	8.842	7.108	(b)	5.248	0.572
CVS1-18	1.433	10.932	7.680	10.562	7.954	2.147

(a) Release rates were normalized using the target compositions given in Table 4.6.

(b) Not detected.

between Si releases and releases of other elements for the 7-day PCT appear to be due to outlying Si releases for some glasses. Correlations between elemental releases from MCC-1 and PCT tests range from roughly 0.60 - 0.80 for Si and Cs (MCC-1 only), B, Li, Mo, and Na. Correlations between PCT Si or Cs releases and MCC-1 releases were roughly in the 0.40 - 0.55 range.

Relatively large correlations exist between T_{10} and η_{1150} (0.840), T_g and ϵ_{1150} (-0.806), and T_{10} and ϵ_{1150} (-0.746) in Table 5.8. Low negative correlation between η_{1150} and ϵ_{1150} (-0.443) is a result of different transport mechanisms of electric charge and mechanical momentum within the glass melt network. Whereas electric charge is transported predominantly by alkali ions moving inside the borosilicate network, viscous flow requires breaking the network bonds.

In Table 5.9, the property transformations increase the correlation between T_{10} and η_{1150} (-0.982) and between η_{1150} and ϵ_{1150} (-0.726). Correlations among normalized MCC-1 and PCT releases remain essentially as strong as they were before transformation. Correlations between MCC-1 and PCT releases increased noticeably from pre-transformation values.

TABLE 5.8. Pairwise Correlations^(a) Among Untransformed Glass Properties

	T_{10}	η_{1150}	ϵ_{1150}	T_g	α_s	α_m	MCC-1, 28-Day				PCT, 7-Day			
							Si	B	Li	Mo	Na	Cs	Si ^(b)	Normalized Release
													B	Li
													Mo	Na
η_{1150}	.840													
ϵ_{1150}	-.746	-.443												
T_g	.623	.549	-.806											
α_s	-.581	-.424	.744	-.683										
α_m	-.747	-.618	.488	-.416	.332									
MCC-1 Si	-.319	-.293	.170	.057	.021	.392								
MCC-1 B	-.276	-.264	.134	.089	.010	.358	.994							
MCC-1 Li	-.280	-.261	.138	.094	.025	.369	.990	.999						
MCC-1 Mo	-.273	-.255	.143	.082	.024	.362	.994	.998	.997					
MCC-1 Na	-.272	-.260	.119	.101	.004	.362	.991	.999	.999	.997				
MCC-1 Cs	-.364	-.311	.084	.056	-.159	.384	.758	.723	.714	.718	.741			
PCT Si ^(b)	-.588	-.366	.665	-.526	.534	.291	.415	.399	.394	.403	.400	.474		
PCT B	-.334	-.344	.168	-.079	-.107	.153	.670	.650	.618	.630	.640	.749	.586	
PCT Li	-.316	-.340	.110	.002	-.157	.182	.715	.702	.674	.683	.697	.793	.544	.986
PCT Mo	-.278	-.289	.128	-.094	-.124	.120	.648	.620	.585	.612	.615	.781	.609	.943
PCT Na	-.315	-.328	.130	-.048	-.119	.173	.708	.689	.658	.673	.684	.809	.589	.987
PCT Cs	-.486	-.344	.415	-.337	.170	.265	.545	.501	.474	.495	.497	.756	.789	.880
													.853	.864

(a) Pearson correlation coefficients take values between -1 and +1, which represent perfect negative and positive pairwise correlation, respectively. A correlation of 0 represents a total lack of pairwise correlation.

(b) Questionable results for PCT normalized Si release on CVS-I glasses 15 and 18 significantly affected correlations with other properties.

TABLE 5.9. Pairwise Correlations^(a) Among Transformed^(b) Glass Properties

	T_{10}	η_{1150}	ϵ_{1150}	T_g	α_s^*	α_m	MCC-1, 28-Day					PCT, 7-Day					
							Normalized Release					Normalized Release					
							Si	B	Li	Mo	Na	Cs	Si ^(c)	B	Li	Mo	Na
η_{1150}	-.982																
ϵ_{1150}	.766	-.726															
T_g	-.622	.625	-.828														
α_s^g	.584	-.539	.763	-.683													
α_s^s	.736	-.737	.523	-.416	.332												
α_m	.475	-.506	.160	-.004	-.033	.493											
MCC-1 Si	.520	-.554	.204	-.037	.012	.451	.978										
MCC-1 B	.531	-.565	.213	-.034	.014	.463	.976	.999									
MCC-1 Li	.518	-.546	.201	-.039	.020	.456	.984	.997	.995								
MCC-1 Mo	.525	-.558	.193	-.031	.010	.461	.978	.999	.999	.997							
MCC-1 Na	.453	-.461	.061	-.036	-.013	.444	.872	.866	.865	.882	.885						
MCC-1 Cs	.597	-.573	.488	-.424	.355	.448	.614	.686	.690	.692	.694	.721	.809				
PCT Si ^(c)	.532	-.559	.263	-.132	.048	.358	.819	.906	.905	.886	.901	.766	.766	.979			
PCT B	.520	-.555	.265	-.127	-.006	.365	.814	.903	.905	.878	.899	.746	.766	.973	.947		
PCT Li	.510	-.522	.235	-.149	.044	.346	.822	.897	.895	.892	.899	.832	.875	.973	.973	.977	
PCT Mo	.537	-.559	.243	-.109	.067	.358	.831	.917	.917	.900	.916	.805	.813	.993	.973	.880	.883
PCT Na	.526	-.527	.284	-.238	.206	.321	.746	.821	.821	.816	.829	.853	.817	.850	.858		
PCT Cs																	

- (a) Pearson correlation coefficients take values between -1 and +1, which represent perfect negative and positive pairwise correlation, respectively. A correlation of 0 represents a total lack of pairwise correlation.
- (b) The property transformations are identified in Table 5.1, and discussed in Section 5.1.
- (c) Questionable results for PCT normalized Si release on CVS-I glasses 15 and 18 significantly affected correlations with other properties.

5.3 FITTED LINEAR MIXTURE MODELS

Linear mixture models of the form (3) were used to relate the glass and melt property data given earlier in Tables 5.2, 5.3, 5.5, and 5.6 to the mass-fraction target compositions given in Table 4.6. Property values were first mathematically transformed as indicated in Table 5.1, and then the models were fitted using unweighted least squares via the REG procedure of SAS (1985a). Model coefficients and goodness-of-fit statistics are discussed in Section 5.3.1, while model validation using other data is discussed in Section 5.3.2.

5.3.1 Model Coefficients and Goodness-of-Fit Statistics

Tables 5.10 through 5.13 contain the coefficients and goodness-of-fit statistics for the fitted linear mixture models. Three goodness-of-fit statistics are included for each model: R^2 , adjusted R^2 (R_A^2), and a yes/no result from a statistical F-test for lack-of-fit. For a given fitted model, R^2 (without adjustment) merely represents the proportion of variation in the response from the transformed property data explained by the fitted model. As such, it must fall between 0.0 and 1.0, with 1.0 denoting a perfect fit. The adjusted R^2 (R_A^2) statistic incorporates a correction for the number of data points and the number of terms used in the model, although it still must lie between 0.0 and 1.0 (Draper and Smith 1981). The LOF yes/no indication gives the results of a statistical lack-of-fit test, which compares the property variation unexplained by a fitted model to property variation from replicate glasses included in CVS-I. If the property variation unexplained by a fitted linear mixture model is significantly larger than replicate variation, then the model is indicated as having a statistically significant lack-of-fit (Draper and Smith 1981).

The R^2 and R_A^2 values in Tables 5.10 through 5.13 range from approximately 0.75 to 0.98, indicating that the linear mixture model form (3) explains large fractions of the variability in property values within the composition region covered by CVS-I. However, the R^2 and R_A^2 values are enough below 1.0 that there appears to be room for improvement. Indeed, statistical tests for model lack-of-fit showed that the fitted linear mixture models for all properties except ϵ_{1150} , T_g , α_s , and α_m had statistically significant

TABLE 5.10. Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to T_{10} , η_{1150} , ϵ_{1150} , T_g , α_s , and α_m ^(a)

Component	T_{10}	η_{1150}	ϵ_{1150}	T_g	α_s	α_m
SiO ₂	0.00036699	9.0354	-1.26176	622.006	0.74723	34.6536
B ₂ O ₃	0.00147939	-6.6671	3.92561	610.705	2.64195	204.4520
Na ₂ O	0.00200507	-11.6822	26.64774	149.530	38.56759	273.1760
Li ₂ O	0.00398172	-34.2429	64.80273	-770.552	51.62066	625.4629
CaO	0.00160469	-4.6522	-0.75219	622.803	18.73964	56.5594
MgO	0.00119727	-1.2066	-3.73613	459.971	11.09192	-113.4390
Fe ₂ O ₃	0.00106193	-0.4086	3.66635	501.516	9.72403	175.7513
Al ₂ O ₃	0.00009101	11.0632	-2.02050	565.935	7.57654	-111.9280
ZrO ₂	0.00045934	8.3702	-0.08843	759.442	7.44074	-119.4520
Others	0.00096563	-0.9875	7.80601	302.374	10.15195	-10.8527
$R^{2(b)}$	0.978	0.977	0.939	0.941	0.914	0.757
$R_A^{2(b)}$	0.962	0.961	0.897	0.900	0.855	0.588
LOF? ^(c)	Yes	Yes	No	No	No	No

- (a) Linear mixture models were fitted to transformations of the glass properties as listed in Table 5.1.
- (b) The R^2 statistic takes a value between 0.0 and 1.0, and indicates the proportion of variation in the property data explained by the model. R_A^2 corrects R^2 for the number of terms in the model, which reduces the value considerably for some properties.
- (c) A statistical F-test for lack-of-fit (LOF) was performed using the estimates of experimental variation obtained from four replicate tests. "Yes" denotes a statistically significant LOF at greater than 99% confidence, while "No" indicates the LOF was not significant at the 90% level.

TABLE 5.11. Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to PCT Normalized Elemental Releases^(a)

Component	PCT Si	PCT B	PCT Li	PCT Mo	PCT Na	PCT Cs
SiO ₂	-2.66001	-2.38107	-0.95633	-1.17863	-2.71474	-3.51765
B ₂ O ₃	-2.00624	8.94664	8.48774	5.76797	8.09470	0.57974
Na ₂ O	7.29642	13.28613	9.17931	10.69454	14.42695	12.52430
Li ₂ O	14.68333	16.33107	12.82360	17.32061	14.15706	14.57005
CaO	-2.97881	-3.86681	-3.40053	-1.25348	0.35008	8.52131
MgO	4.18028	13.47469	7.03008	16.12771	14.55662	10.01496
Fe ₂ O ₃	-1.19436	-4.93704	-6.71507	-5.87287	-5.95689	-7.58789
Al ₂ O ₃	-14.54570	-25.10090	-22.17110	-28.36820	-25.41050	-24.48850
ZrO ₂	-8.42243	-7.93660	-8.71632	12.26360	-9.59620	-16.39180
Others	-0.48690	1.43290	3.18971	1.01428	0.64639	-0.46803
R ^{2(b)}	0.890	0.952	0.924	0.960	0.962	0.835
R _A ^{2(b)}	0.814	0.920	0.871	0.932	0.935	0.721
LOF? ^(c)	Yes	Yes	Yes	Yes	Yes	Yes

- (a) Linear mixture models were fitted to transformations of the glass properties as listed in Table 5.1 (natural logarithms in the case of PCT normalized releases). Results from duplicate PCT leach tests were averaged prior to transforming and fitting the data.
- (b) The R² statistic takes a value between 0.0 and 1.0, and indicates the proportion of variation in the property data explained by the model. R_A² corrects R² for the number of terms in the model, which reduces the value considerably for some properties.
- (c) A statistical F-test for lack-of-fit (LOF) was performed using the estimates of experimental variation obtained from four replicate tests. "Yes" denotes a statistically significant LOF at greater than 99% confidence, while "No" indicates the LOF was not significant at the 90% level.

TABLE 5.12. Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to MCC-1 Normalized Elemental Releases from All CVS-I Glasses^(a)

Component	MCC-1 Si	MCC-1 B	MCC-1 Li	MCC-1 Mo	MCC-1 Na	MCC-1 Cs
SiO ₂	2.53002	2.18996	2.10699	2.40173	2.15395	2.34592
B ₂ O ₃	8.82810	11.73804	11.66585	11.01195	11.49900	6.68180
Na ₂ O	8.69854	12.83780	12.64100	12.17658	12.49891	8.77320
Li ₂ O	10.72237	14.69046	13.97544	15.39715	13.98640	10.29496
CaO	1.04460	2.26417	2.30650	2.96982	3.19633	8.69591
MgO	2.77005	6.63564	5.85573	6.98409	7.03104	11.12576
Fe ₂ O ₃	0.33332	-0.99994	-0.61475	-1.07519	-0.65775	2.58107
Al ₂ O ₃	-11.40850	-16.39450	-15.80750	-16.39220	-16.05200	-12.41570
ZrO ₂	-7.98994	-8.47059	-8.28609	-9.14658	-8.88352	-10.74320
Others	-0.89544	0.72346	1.24593	-0.17051	0.53166	-3.00774
R ² ^(b)	0.854	0.890	0.902	0.873	0.902	0.947
R _A ² ^(b)	0.752	0.814	0.834	0.785	0.834	0.911
LOF? ^(c)	Yes	Yes	Yes	Yes	Yes	Yes

- (a) Linear mixture models were fitted to transformations of the glass properties as listed in Table 5.1 (natural logarithms in the case of MCC-1 normalized releases). Results from duplicate MCC-1 leach tests were averaged prior to transforming and fitting the data.
- (b) The R² statistic takes a value between 0.0 and 1.0, and indicates the proportion of variation in the property data explained by the model. R_A² corrects R² for the number of terms in the model, which reduces the value considerably for some properties.
- (c) A statistical F-test for lack-of-fit (LOF) was performed using the estimates of experimental variation obtained from four replicate tests. "Yes" denotes a statistically significant LOF at greater than 99% confidence, while "No" indicates the LOF was not significant at the 90% level.

TABLE 5.13. Coefficients and Goodness-of-Fit Statistics for Linear Mixture Models Fitted to MCC-1 Normalized Elemental Releases After Deleting the High Release Data Corresponding to Glasses CVS1-4,6,9,13,15,21^(a)

Component	MCC-1 Si	MCC-1 B	MCC-1 Li	MCC-1 Mo	MCC-1 Na	MCC-1 Cs
SiO ₂	0.02716	-1.76175	-1.10865	-1.37147	-1.35776	0.18302
B ₂ O ₃	6.68572	7.86846	8.20832	6.97583	7.82077	3.72453
Na ₂ O	7.88338	11.80380	11.73557	11.19321	11.43679	9.03282
Li ₂ O	5.92782	12.80191	12.19256	12.51176	12.55445	12.28868
CaO	6.41171	8.03510	7.66883	9.59755	8.61848	0.99668
MgO	1.84915	2.70415	3.39482	5.00321	4.08764	7.89935
Fe ₂ O ₃	7.82548	10.06372	8.31600	9.53735	9.08298	8.01913
Al ₂ O ₃	-0.99128	-1.01657	-3.07654	-1.59965	-2.35625	-4.38258
ZrO ₂	0.68112	5.98820	3.45698	3.96076	3.96583	-2.74488
Others	-4.57434	-1.57788	-1.10686	-2.90895	-1.39905	-3.41565
R ² ^(b)	0.977	0.964	0.956	0.972	0.968	0.984
R _A ² ^(b)	0.947	0.918	0.900	0.937	0.928	0.963
LOF? ^(c)	Yes	Yes	Yes	Yes	Yes	Yes

- (a) Linear mixture models were fitted to transformations of the glass properties as listed in Table 5.1 (natural logarithms in the case of MCC-1 normalized releases). Results from duplicate MCC-1 leach tests were averaged prior to transforming and fitting the data.
- (b) The R² statistic takes a value between 0.0 and 1.0, and indicates the proportion of variation in the property data explained by the model. R_A² corrects R² for the number of terms in the model, which reduces the value considerably for some properties.
- (c) A statistical F-test for lack-of-fit (LOF) was performed using the estimates of experimental variation obtained from four replicate tests. "Yes" denotes a statistically significant LOF with greater than 99% confidence (95% for MCC-1 Cs), while "No" indicates the LOF was not significant at the 90% level.

lack-of-fits. The model lack-of-fits for these properties was not statistically significant due to the higher uncertainty in data values for these properties, as summarized in Table 5.14.

Also, although not shown in this report, graphical statistical analyses of the residuals (a residual is the difference between the predicted and observed values of a property for a given data point) were performed. These analyses clearly indicated the need for second-order terms in the mixture models to account for interactive and nonlinear blending effects of the components. The need for second-order terms was anticipated based on theory and previous experience.

5.3.2 Model Validation

In order to better understand the predictive ability of the fitted linear mixture models, it is desirable to apply the fitted models to some data not used to develop the models. In this way an independent assessment of model predictive ability (referred to as validation) is obtained. No extra points were included in the CVS-I for this purpose, but it was possible to perform some independent assessments using data from past experimental work. Although this other data is far from an ideal validation data set, it was all that was available at the time this work was done. The compositions of these other glasses are given in Table 5.15. Note that the compositions are divided into three groups, according to whether the composition was inside, marginally outside, or notably outside the CVS-I region defined in Table 4.5.

Table 5.16 lists the measured and predicted property values obtained from the fitted models. Note that only data on T_{10} , η_{1150} , ϵ_{1150} , and the 28-day MCC-1 elemental releases are included in Table 5.16. A larger and more complete validation data set will be compiled as part of CVS-II work. When comparing the measured and predicted property values in Table 5.16, keep in mind that the data being used to validate and assess the predictive abilities of the models were collected prior to the data used to fit the model, and could be subject to more sources of uncertainty.

Agreement between measured and predicted values of T_{10} , η_{1150} , and ϵ_{1150} is fairly good for validation compositions inside or only marginally outside

TABLE 5.14. Standard Deviations of Untransformed and Transformed Glass and Melt Property Data from Replicate Glasses

Property	Replicate Glasses	Untransformed Property			Transformed Property		
		Mean	SD	%RSD	Mean	SD	%RSD
T_{10}	1,19,20	1086.0	2.646	0.24	9.21E-4	2.25E-6	0.24
	4,21	1139.5	2.121	0.19	8.78E-4	1.63E-6	0.19
	8,22	<u>1258.0</u>	<u>1.414</u>	<u>0.11</u>	<u>7.95E-4</u>	<u>8.94E-7</u>	<u>0.11</u>
	Pooled	---	2.264	0.20	---	1.84E-6	0.20
η_{1150}	1,19,20	5.75	0.071	1.2	1.734	0.027	1.56
	4,21	9.15	0.495	5.41	2.213	0.054	2.45
	8,22	<u>36.10</u>	<u>0.141</u>	<u>0.39</u>	<u>3.586</u>	<u>0.004</u>	<u>0.11</u>
	Pooled	---	0.279	2.85	---	0.033	1.65
ϵ_{1150}	1,19,20	23.30	4.190	17.98	4.814	0.443	9.20
	4,21	8.60	0.707	8.22	2.931	0.121	4.12
	8,22	<u>9.00</u>	<u>0.283</u>	<u>3.14</u>	<u>3.000</u>	<u>0.047</u>	<u>1.57</u>
	Pooled	---	2.988	13.45	---	0.320	6.87
T_g	1,19,20	491.3	5.05	1.03	T_g was not transformed		
	4,21	534.0	13.36	2.50			
	8,22	<u>553.4</u>	<u>9.12</u>	<u>1.65</u>			
	Pooled	---	8.84	1.66			
α_s	1,19,20	8.90	0.600	6.74	α_s was not transformed		
	4,21	6.25	0.919	14.71			
	8,22	<u>7.60</u>	<u>0.707</u>	<u>9.30</u>			
	Pooled	---	0.718	9.92			
α_m	1,19,20	94.13	7.91	8.40	α_m was not transformed		
	4,21	85.35	22.13	25.93			
	8,22	<u>64.50</u>	<u>21.63</u>	<u>33.55</u>			
	Pooled	---	16.46	22.02			
MCC-1 B	1,19,20	12.66	0.309	2.44	2.538	0.024	0.96
	4,21	197.75	11.370	5.75	5.286	0.058	1.09
	8,22	<u>17.62</u>	<u>0.368</u>	<u>2.09</u>	<u>2.869</u>	<u>0.021</u>	<u>0.73</u>
	Pooled	---	5.69	3.51	---	0.0351	0.94
	w/o 4,21	---	0.40	2.33	---	0.0232	0.89
PCT B	1,19,20	0.500	0.039	7.74	-0.696	0.079	-11.39
	4,21	19.744	1.265	6.41	2.982	0.064	2.15
	8,22	<u>1.178</u>	<u>0.084</u>	<u>7.14</u>	<u>0.163</u>	<u>0.072</u>	<u>43.84</u>
	Pooled	---	0.634	7.28	---	0.0738	---

TABLE 5.15. Glass Compositions^(a) Used to Assess Predictive Ability of Fitted Linear Mixture Models

Glass	SiO ₂	B ₂ O ₃	Na ₂ O	Li ₂ O	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	ZrO ₂	(b) Others
I. Compositions Inside the CVS-I Region of Table 4.5										
NCAW87-2	.5278	.1053	.1125	.0450	.0083	.0084	.0719	.0231	.0385	.0592
NCAW87-3	.5353	.1053	.1050	.0375	.0120	.0122	.0719	.0231	.0385	.0592
NCAW87-4	.5353	.1053	.1125	.0375	.0083	.0084	.0719	.0231	.0385	.0592
HW39-2	.5122	.0956	.1050	.0375	.0289	.0084	.1172	.0453	.0063	.0436
HWVS2	.5188	.0983	.1124	.0371	.0279	.0089	.0863	.0311	.0076	.0716
HWVS4	.5583	.0967	.0738	.0379	.0277	.0082	.1486	.0000	.0030	.0458
HWVS5	.5215	.0973	.1113	.0361	.0281	.0084	.0873	.0311	.0076	.0713
HWVS7	.5576	.0946	.0735	.0362	.0292	.0086	.0483	.0855	.0072	.0593
HWVS10	.5214	.0949	.1139	.0380	.0280	.0095	.0849	.0320	.0073	.0701
LOWAL	.5130	.0956	.107	.0375	.0290	.0085	.1288	.0240	.0069	.0489
HIGHZR	.5092	.0956	.0941	.0375	.0286	.0080	.0718	.0278	.1000	.0274
HIGHNA	.5112	.0956	.1320	.0375	.0288	.0083	.1025	.0396	.0055	.0390
LOWFE	.5143	.0956	.1126	.0375	.0291	.0086	.0800	.0576	.0079	.0568
LOWFE1	.5158	.0956	.1179	.0375	.0292	.0088	.0550	.0661	.0091	.0650
II. Compositions Marginally Outside the CVS-I Region of Table 4.5										
HWVS6	.5046	.0983	.0742	.0361	.0281	.0071	.1455	.0021	.0853	.0187
HWVS8	.5060	.0957	.1700	.0356	.0285	.0079	.0519	.0945	.0000	.0199
HWVS9	.5504	.0962	.1784	.0371	.0275	.0085	.0501	.0018	.0028	.0472
HWVS11	.5495	.0949	.1758	.0370	.0271	.0078	.0509	.0539	.0005	.0026
HWVS12	.5032	.0963	.0717	.0334	.0285	.0118	.1504	.0845	.0000	.0202
HWVS14	.5096	.0962	.0753	.0367	.0297	.0092	.1309	.0000	.0122	.1002
III. Compositions Notably Outside the CVS-I Region of Table 4.5										
HWVS1	.5144	.0967	.0738	.0369	.0299	.0110	.0484	.0000	.0199	.1690
HWVS3	.5070	.0974	.0733	.0371	.0296	.0110	.0502	.0000	.0191	.1753
HWVS13	.5071	.0958	.1744	.0363	.0272	.0071	.1522	.0000	.0000	.0000
HWVS15	.5082	.0971	.0753	.0357	.0293	.0089	.1110	.0000	.0123	.1222

- (a) These compositions and the corresponding property data in Table 5.16 are from past experimentation, and were not used to fit the linear mixture models.
- (b) The "Others" values were obtained by subtracting the sum of the rest of the components from one. The oxides grouped into "Others" in these compositions may differ in number and relative proportions from those used in CVS-I. This could affect the predictive ability of the fitted models.

TABLE 5.16. Comparison of Measured Property Values to Predicted Values from the Fitted Linear Mixture Models for Compositions in Table 5.15

Glass	T ₁₀ (°C)	η ₁₁₅₀ (Pa·s)	ε ₁₁₅₀ (S/m)	MCC-1 28-day Normalized Releases (g/m ²)					
				Si	B	Li	Mo	Na	Cs
I. Compositions Inside the CVS-I Region of Table 4.5									
NCAW87-2									
meas.	1060	4.5	29.6	--	--	--	--	--	--
pred.	1074	5.2	39.7	23.5	46.4	44.9	42.7	42.1	17.5
rmod.	na	na	na	9.4	15.3	17.0	13.2	15.4	10.8
NCAW87-3									
meas.	1121	6.7	25	--	--	--	--	--	--
pred.	1112	7.7	31.2	21.0	39.7	38.6	36.7	36.5	16.7
rmod.	na	na	na	8.7	13.1	14.7	11.6	13.3	9.9
NCAW87-4									
meas.	1111	6.0	25.9	13.3	19.3	16.5	16.7	16.0	20.7
pred.	1106	7.2	33.7	22.1	42.3	41.1	38.8	38.5	16.5
rmod.	na	na	na	8.9	13.7	15.4	11.9	13.9	9.9
HW39-2									
meas.	1088	--	29	12.9	15.0	15.7	--	15.5	20.6
pred.	1088	6.0	31.1	18.9	29.4	29.2	28.5	28.6	20.8
rmod.	na	na	na	13.2	18.7	19.4	17.7	18.7	16.7
HWVS2									
meas.	1108	--	31	13.9	16.8	16.7	--	17.0	15.3
pred.	1074	5.0	34.7	23.5	44.3	43.7	41.6	42.0	22.7
rmod.	na	na	na	9.9	14.6	16.7	13.5	15.4	13.5
HWVS4									
meas.	1118	--	20	33.9	47.5	45.2	--	50.1	80.5
pred.	1106	7.5	24.5	28.5	46.4	45.6	46.2	45.3	34.4
rmod.	na	na	na	13.7	16.8	18.9	16.6	18.0	19.9
HWVS5									
meas.	1103	--	48	13.5	16.2	16.5	--	16.7	15.4
pred.	1081	5.4	33.5	23.0	42.6	42.1	40.1	40.5	22.2
rmod.	na	na	na	9.8	14.2	16.3	13.2	15.0	13.2
HWVS7									
meas.	1307	--	24	8.2	8.6	8.6	--	8.9	10.1
pred.	1230	22.0	19.2	9.6	11.7	11.8	11.6	11.4	8.3
rmod.	na	na	na	5.3	5.5	6.1	5.3	5.7	5.7
HWVS10									
meas.	1113	--	36	13.2	15.5	15.2	--	16.0	14.7
pred.	1073	5.0	35.4	23.4	43.9	43.2	41.4	41.6	22.9
rmod.	na	na	na	9.8	14.4	16.5	13.4	15.2	13.6

Note: meas. = measured value
pred. = predicted values using linear mixture models fitted to all CVS-I data
rmod. = predicted MCC-1 28-day normalized release values using linear mixture models fitted to a reduced set of CVS-I data

TABLE 5.16. (contd)

Glass	T_{10} (°C)	η_{1150} (Pa·s)	ϵ_{1150} (S/m)	MCC-1 28-day Normalized Releases (g/m ²)					
				Si	B	Li	Mo	Na	Cs
I. Compositions Inside the CVS-I Region of Table 4.5 (continued)									
LOWAL									
meas.	1063	4.1	--	--	--	--	--	--	--
pred.	1062	4.6	33.4	24.7	42.8	42.3	41.1	41.4	28.0
rmod.	na	na	na	14.8	22.0	23.5	20.8	22.5	20.3
HIGHZR									
meas.	1158	10.4	--	--	--	--	--	--	--
pred.	1146	12.5	25.3	9.9	15.8	15.4	14.7	14.5	7.9
rmod.	na	na	na	9.9	19.0	17.4	15.8	16.9	9.2
HIGHNA									
meas.	1048	3.7	--	--	--	--	--	--	--
pred.	1051	4.1	38.7	25.6	46.4	45.3	44.4	44.4	27.7
rmod.	na	na	na	14.9	22.4	24.0	21.2	22.7	19.8
LOWFE									
meas.	1104	6.3	--	--	--	--	--	--	--
pred.	1098	6.5	32.7	17.1	27.6	27.4	26.3	26.4	16.5
rmod.	na	na	na	9.8	13.7	14.9	12.8	14.0	12.0
LOWFE1									
meas.	1111	6.9	--	--	--	--	--	--	--
pred.	1105	6.9	33.8	15.9	26.4	26.1	24.9	25.0	14.1
rmod.	na	na	na	8.0	11.2	12.4	10.4	11.5	9.7

II. Compositions Marginally Outside the CVS-I Region of Table 4.5

HWVS6									
meas.	1175	--	22	10.0	11.4	11.2	--	11.7	9.8
pred.	1125	10.2	22.0	12.8	19.4	19.2	18.4	18.4	13.0
rmod.	na	na	na	16.0	30.3	26.5	25.8	26.7	16.4
HWVS8									
meas.	1028	--	48	12.0	13.2	13.6	--	13.8	8.8
pred.	1055	4.4	44.9	21.6	37.8	36.5	36.0	35.9	21.0
rmod.	na	na	na	13.9	19.7	21.1	18.9	19.6	16.1
HWVS9									
meas.	999	--	64	165.4	268.0	238.3	--	251.9	216.8
pred.	996	2.3	53.8	65.0	184.8	171.6	172.2	168.4	63.4
rmod.	na	na	na	14.2	21.3	28.0	20.7	24.0	22.7

Note: meas. = measured value
 pred. = predicted values using linear mixture models fitted to all CVS-I data
 rmod. = predicted MCC-1 28-day normalized release values using linear mixture models fitted to a reduced set of CVS-I data

TABLE 5.16. (contd)

Glass	T_{10} (°C)	η_{1150} (Pa·s)	ϵ_{1150} (S/m)	MCC-1 28-day Normalized Releases (g/m ²)					
				Si	B	Li	Mo	Na	Cs

II. Compositions Marginally Outside the CVS-I Region of Table 4.5 (continued)

HWVS11									
meas.	1039	--	50	14.6	14.6	14.8	--	15.7	13.5
pred.	1046	4.3	46.4	36.6	73.3	68.6	71.3	68.7	37.3
rmod.	na	na	na	16.1	20.5	23.9	20.7	21.5	20.5
HWVS12									
meas.	1158	--	23	12.5	11.3	12.6	--	12.5	--
pred.	1176	13.9	18.4	9.4	9.6	9.9	9.7	9.8	11.6
rmod.	na	na	na	13.8	16.5	15.0	16.0	15.5	14.6
HWVS14									
meas.	1141	--	26	34.5	50.7	49.9	--	52.7	58.2
pred.	1079	5.1	28.3	22.2	41.2	41.5	38.4	39.5	23.2
rmod.	na	na	na	9.5	15.1	17.0	13.6	16.0	14.2

III. Compositions Notably Outside the CVS-I Region of Table 4.5

HWVS1									
meas.	1314	--	24	40.2	69.6	67.6	--	73.0	66.7
pred.	1097	5.5	30.5	19.3	44.6	45.1	39.2	41.0	14.4
rmod.	na	na	na	3.6	6.1	8.1	5.2	7.0	5.7
HWVS3									
meas.	1238	--	27	42.4	74.0	69.9	--	77.1	73.5
pred.	1091	5.1	31.2	19.0	44.5	45.2	38.9	40.8	14.0
rmod.	na	na	na	3.6	6.2	8.2	5.2	7.1	5.7
HWVS13									
meas.	929	--	66	82.6	121.8	117.9		117.9	--
pred.	966	1.6	52.5	62.4	143.1	135.4	137.3	136.7	85.0
rmod.	na	na	na	37.5	63.6	67.5	62.0	63.9	57.2
HWVS15									
meas.	1156	--	27	33.9	53.7	52.7	--	53.8	58.4
pred.	1084	5.1	28.8	21.4	42.2	42.8	38.6	40.1	20.3
rmod.	na	na	na	7.3	11.8	14.0	10.5	12.9	11.1

Note: meas. = measured value
pred. = predicted values using linear mixture models fitted to all CVS-I data
rmod. = predicted MCC-1 28-day normalized release values using linear mixture models fitted to a reduced set of CVS-I data

the CVS-I region. Agreement for T_{10} and ϵ_{1150} was also fairly good for compositions notably outside the CVS-I, with the exception of underprediction of larger T_{10} values. It is not possible to judge η_{1150} prediction performance for the "notably outside" compositions, because no measured values were available.

Table 5.16 contains predicted 28-day MCC-1 normalized release values for Si, B, Li, Mo, Na, and Cs using the linear models fitted to all CVS-I data and to the reduced data set (without #4, 6, 9, 13, 15, 21). Focusing on B release and glasses inside or moderately outside the CVS-I region, the model fitted to all CVS-I data tends to predict fairly well releases less than 12 g/m² and between 40-70 g/m², overpredict releases in the range 13-40 g/m², and underpredict releases above 100 g/m².^(a) This behavior is due to the large composition region explored, the presence of a few glasses with large normalized releases, and the inability of the linear mixture model form to properly account for the significant increase in release that occurs over the region.

The linear mixture models fitted to the reduced set of MCC-1 release data correct for the overprediction of small-to-moderate releases fairly well, but severely underpredict moderate-to-large releases. This is understandable given that six of the eight glasses with moderate-to-large releases were deleted in forming the reduced data set.

In summary, the fitted linear mixture models explain much of the variation in the properties of interest, but have statistically significant lack-of-fits and yield biased property predictions in some cases. These problems should be reduced or eliminated in CVS-II by reducing the size of the region studied (to eliminate compositions with property values far removed from acceptable levels) and by including second-order terms in the mixture models (when sufficient data become available). Still, the fits were deemed sufficiently acceptable for the models to be used for preliminary investigations, provided that 1) results be considered as having considerable uncertainty and

(a) These observations are similar to, and based in part on, observations made from the CVS-I data used to fit the full and reduced release models.

treated accordingly, and 2) the fitted models are only applied within the region defined by the single- and multiple-component constraints listed in Table 4.5.

5.4 CVS-II COMPOSITION REGION AND THE QCR

Implications of the CVS-I results for CVS-II and the development of a QCR are discussed below.

5.4.1 CVS-II Components and Composition Region

Although the fitted linear mixture models had statistically significant lack-of-fits, and in some cases considerable prediction biases, the fits were deemed good enough to use as a basis for planning CVS-II.

The first issue of interest was whether the number of components to be studied in CVS-II could be reduced from the 10 considered in CVS-I. To answer this question, the component effects plots for the glass and melt properties were considered to see if there were any components having negligible effects for all properties (allowing such components to be fixed or absorbed into the "Others" component), or if there were pairs of components having similar effects for all properties (allowing such components to be combined into a single component). Component effects plots based on linear mixture models fitted to component mole fractions were considered as well as those based on component mass fractions (presented earlier in Figures 5.1 - 5.8, 5.10, 5.11). While there were components with negligible effects and similar effects for some properties, these findings did not hold for all properties. There were some differences between effects plots based on mole and mass fractions, but the general conclusions were the same. Hence, it was concluded that the number of components could not be reduced for CVS-II. The fitted linear mixture models were also used to develop a preliminary definition of the composition region to be studied in CVS-II.

5.4.2 Qualified Composition Region

An important final goal of the CVS work (after CVS-II) is to develop a QCR that includes with high confidence only those compositions that meet radionuclide and elemental release limits and processing restrictions. Fitted

property models and statistical confidence statements that take into account the uncertainty in fitted model predictions can be used to reach this goal, provided adequate property models are obtained. Model adequacy needs to be assessed from both statistical and practical perspectives. That is, one needs to consider whether a model has a statistically significant lack-of-fit and if so, whether it is practically significant.

The linear mixture models developed from CVS-I data are not deemed adequate in the sense discussed above, and hence, it is not appropriate to develop a QCR (preliminary or final) based on CVS-I models.

6.0 EFFECT OF HWVP RECYCLE STREAMS ON GLASS PROPERTIES

Zeolite loaded with Cs and Sr from transuranic (TRU) waste sorption and filter precoat materials (diatomaceous earth) can be added to the melter feed. In this section, CVS-I mixture models are used to assess the impact of these additions on glass properties.

Two types of recycle streams are considered: the recycle material from filtration and ion exchange of treated submerged bed scrubber tank (SBS) effluent and the recycle from decontamination waste transfer tank (DWTT) evaporation/bottoms. Both recycle streams contain SBS process solids, zeolite, and diatomaceous earth. The DWTT evaporation/bottoms recycle also contains significant amounts of decontamination chemicals. The flowsheet compositions of the TRU recycle stream per plant batch for each scenario are presented in Table 6.1. The composition of the process solids was assumed to be the same as that of the precipitated solids found in the SBS tank during the PSCM-23 melter run (Goles and Nakaoka 1988). The zeolite was assumed to be Linde Ionsiv^(a) IE-96.^(b) The diatomaceous earth was assumed to be Manville Corp Standard Super-Cell.^(c) The composition of these materials is shown in Table 6.2.

The addition of these TRU recycle streams will be made to the Slurry Mix Evaporator tank (SME) for batch processing. The nominal amounts of waste from the slurry receipt and adjustment tank (SRAT) and added process frit are provided in Table 6.1. The waste and frit used in this evaluation were NCAW'87 (Table 4.2) and HW-39-4 frit, respectively. A 25 wt% waste loading, not counting TRU recycle, was considered.

With one nominal addition of the SBS recycle, the sum of refractory oxides (SiO_2 , Al_2O_3 , and ZrO_2) increases by 0.25 wt% and fluxing oxides decrease by 0.5 wt%. This change in the glass composition is within normally expected analytical error of ICP. At four times the nominal SBS recycle

-
- (a) Trademark of Union Carbide Co., New York, NY.
 - (b) L. A. Bray, personal communication (1984).
 - (c) Manville Corp technical literature.

TABLE 6.1. Content of Feed to Slurry Mix Evaporator Tank (SME)
with TRU Recycle Streams^(a)

Stream	Mass, kg
NCAW'87 waste oxides from SRAT ^(b)	2884
Frit oxides (HW39-4 frit)	8652
SBS treated TRU recycle ^(b)	
Process solids	26
Zeolite (IE-96)	182
Diatomaceous earth	47
DWTT Evaporation/Bottoms TRU recycle ^(c)	
Process solids	26
Zeolite (IE-96)	44
Diatomaceous earth	20
Chemicals	
KNO ₃	1.5
NaNO ₃	125
Mn(OH) ₂	1.3
Total chemicals	128

- (a) S. D. Sharp, personal communication (1988)
(b) Slurry receipt and adjustment tank (SRAT).
(c) Either the treated SBS recycle or DWTT evaporation/bottoms recycle is added, not both.

TABLE 6.2. Composition (Mass Fractions) of SBS Process Solids, Zeolite, Diatomaceous Earth, and DWTT Chemicals

<u>Oxide</u>	<u>SBS Process Solids</u>	<u>Zeolite (IE-96)</u>	<u>Diatomaceous Earth</u>	<u>DWTT Decontamination Chemicals</u>
SiO ₂	0.136	0.674	0.911	
B ₂ O ₃	0.024			
Na ₂ O	0.164	0.079		0.958
Li ₂ O	0.007			
CaO	0.017	0.012	0.005	
MgO	0.033	0.008	0.006	
Fe ₂ O ₃	0.326	0.040	0.013	
ZrO ₂	0.039			
Al ₂ O ₃	0.044	0.173	0.040	
NiO	0.027			
La ₂ O ₃	0.052			
Nd ₂ O ₃	0.034			
MoO ₃	0.023			
CeO ₂	0.024			
CuO	0.005			
MnO ₂	0.006			0.027
Cr ₂ O ₃	0.009			
BaO	0.006	0.001		
SrO	0.005			
K ₂ O		0.010		0.015
P ₂ O ₅			0.002	
TiO ₂	0.009	0.002	0.002	
	-----	-----	-----	-----
	0.990	0.999	0.979	1.000

addition, the amounts of SiO_2 and Al_2O_3 in glass increase by 1.03 and 0.85 wt%, respectively, and B_2O_3 and the alkalis (Na_2O and Li_2O) decrease by 0.83 and 0.71 wt%, respectively. The predicted T_{10} and ϵ_{1150} are presented in Table 6.3.

The model predicts that one nominal amount of treated SBS recycle waste increases the T_{10} of the glass by 9°C . Because the T_{10} value of the HW-39-4 reference glass (1111°C) is near the middle of the acceptable range (1050°C through 1150°C), up to four times the nominal amount of the recycle could be added to the HW-39-4 reference glass composition without exceeding the viscosity limit. The ϵ_{1150} of the glass decreased less than 2 S/m for each nominal addition, which is the uncertainty of the electrical conductivity measurements. Hence, the variation of viscosity would be the limiting factor on the maximum amount of recycle.

The major component of the DWT evaporation/bottoms waste is sodium from the chemical portion of the recycle stream. Twice the nominal amount is the maximum expected of this recycle stream. The T_{10} model predicts that one nominal amount decreases the T_{10} of the glass by 9°C . The ϵ_{1150} of the glass increased less than 3 S/m for each addition. The variation of viscosity would be the limiting factor on the maximum amount of recycle.

Three ways of compensating for the effect of recycle wastes on glass viscosity can be considered:

- 1) **Frit composition adjustment.** If added in a consistent amount and with a constant composition, the effects of the recycle waste on glass viscosity can be compensated for by minor adjustment in the frit composition.

TABLE 6.3. Predicted Values of T_{10} and ϵ_{1150} for Multiple Nominal Additions of Treated SBS Recycle Waste to the HW-39-4 Reference Glass

	Number of Nominal Additions of Treated SBS Recycle Waste				
	0	1	2	3	4
T_{10} ($^\circ\text{C}$)	1111	1120	1129	1147	1155
ϵ_{1150} (S/m)	33	32	30	29	28

- 2) **Adjusting single-component constraints for Al_2O_3 and Na_2O .** At twice the nominal amount of treated SBS recycle (the maximum expected), a reduction of 1.6 wt% Al_2O_3 should be made from the maximum acceptable range in the HWVP feed specification. If a frit composition adjustment is not an option, a reduction of 1.6 wt% Na_2O should be made from the maximum acceptable range in the HWVP feed specification for the DWTT evaporation/bottoms recycle addition.
- 3) **Melting temperature adjustment.** If the amount or composition of a recycle is not expected to be constant, the upper T_{10} limit of 1150°C would need to be reduced to 1140°C to account for SBS recycle variability and the lower T_{10} limit of 1050°C would need to be increased to 1060°C to account for DWTT evaporation/bottoms recycle variability.

7.0 CONCLUSIONS AND RECOMMENDATIONS

7.1 CONCLUSIONS

Experimental data from the statistically-designed CVS-I (involving 10 glass components) were used to develop first-order models for melt and glass properties (viscosity, electrical conductivity, glass transition temperature, thermal expansion, and normalized elemental releases) as a function of glass composition. Based on the results from CVS-I, the following conclusions are made.

7.1.1 Applicability of Linear Mixture Models

The fitted linear mixture models generated from the CVS-I data explain much of the variation in the properties of interest: R^2 values range from approximately 0.75 to 0.98. However, most of the models have statistically significant lack-of-fits. This is partly due to the inability of the linear mixture model to capture the interactive and nonlinear blending effects of the glass components, and partly due to the highly non-linear behavior of certain glasses that are far away from the acceptable region. Reducing the size of the composition region studied in CVS-II and the use of mixture models containing second-order terms should resolve this issue in CVS-II.

Although the linear mixture models had statistically significant lack-of-fits, it was concluded that they are adequate for use in assessing component effects, developing the preliminary CVS-II composition region, providing some input to the HWVP NCAW feed specification, developing glasses, designing the CVS-II test matrix, and other preliminary investigations. The models have considerable uncertainty and bias (in some cases), and this should be considered when putting them to use.

7.1.2 Viscosity

Viscosity at 1150°C (η_{1150}) of the HW-39-4 reference glass is increased by three of the 10 major components in the order (based on mass fraction):

Three other components reduce η_{1150} in the order:

Fe_2O_3 , Others, MgO, and CaO appear to slightly reduce η_{1150} , although their effects could be negligible or slightly positive given the uncertainty in the fitted linear models used to produce the effects plots.

7.1.3 Electrical Conductivity

Electrical conductivity at 1150°C (ϵ_{1150}) of the HW-39-4 reference glass is increased by two components in the order

and decreased by SiO_2 . MgO, Al_2O_3 , CaO, and ZrO_2 appear to have mild to negligible reducing effects on ϵ_{1150} . Fe_2O_3 , B_2O_3 , and "Others" have essentially negligible effects on ϵ_{1150} .

7.1.4 Glass Transition Temperature and Thermal Expansion

Glass transition temperature (T_g) is strongly decreased by Li_2O , and to a lesser extent by Na_2O . T_g is increased by SiO_2 and ZrO_2 . All other components have moderate to negligible effects.

Alkali oxides (Li_2O more than Na_2O) increase and SiO_2 decreases thermal expansion of both solid and molten CVS-I glasses. Al_2O_3 , ZrO_2 , and MgO increase the thermal expansion of molten glasses even more than SiO_2 , but these oxides have little effect on the thermal expansion of solid glass. The remaining components have moderate to negligible effects.

7.1.5 Crystallization

All but one of the glasses that failed the liquidus criterion had the sum of the mass fractions of Fe_2O_3 , Al_2O_3 , ZrO_2 , and "Others" equal to 0.24 (the maximum allowed level). The major crystalline phases observed after 24 hours at 1050°C were various silicates [$MgSiO_3$, $ZrSiO_4$, $Ca_2Zr(SiO_3)_4$], spinels, ZrO_2 (incompletely dissolved), and RuO_2 (undissolved).

7.1.6 Elemental Release

Normalized MCC-1 and PCT release values of B and Li were relatively high for glasses with high B_2O_3 content unless the glass was rich in Al_2O_3 . These glasses are likely to be phase separated. Since these glasses are far outside of the region of acceptable glasses, first-order models were fitted without them (for MCC-1) as well as with them (for MCC-1 and PCT).

Based on the model fitted to all the MCC-1 data, normalized B release of the HW-39-4 reference glass is increased most by Li_2O , followed closely by Na_2O and B_2O_3 . Normalized B release is decreased most by Al_2O_3 and ZrO_2 . Based on the model fitted to a reduced set of CVS-I glasses, normalized B release of the HW-39-4 reference glass is reduced by SiO_2 and to a lesser extent Al_2O_3 and Others. Normalized B release is increased most by Li_2O and Na_2O (almost identical effects), as well as by Fe_2O_3 , B_2O_3 , CaO , and possibly even ZrO_2 .

Results for the PCT model fitted to all CVS-I data were quite similar to those for the MCC-1 model fitted to all CVS-I data, with one exception. Increasing MgO appeared to strongly increase PCT normalized B release, whereas it appeared to have only a moderate effect on MCC-1 B release.

7.1.7 Effect of Li_2O

Whereas Li_2O affects viscosity and electrical conductivity of molten glass considerably more than Na_2O , the effects of Li_2O and Na_2O on glass durability are almost equal. These results favor using Li_2O rather than Na_2O to adjust viscosity and electrical conductivity of the melt while minimizing the deleterious effect on glass durability.

7.1.8 Recycle Addition

The CVS-I model predicts a slight change in T_{10} (the temperature at which viscosity is 10 Pa·s) by the addition of the nominal amount of treated SBS recycle waste (an approximately 9°C increase) and/or the nominal amount of DWTT evaporation/bottom recycle waste (an approximately 9°C decrease).

7.2 RECOMMENDATIONS

Based on the work reported herein and the Section 7.1 conclusions, the following recommendations are made.

7.2.1 Recommendations for CVS-II

The following recommendations are made for implementation in CVS-II.

- Continue to study the effect of glass composition on melt and glass properties in terms of the 10 components (SiO_2 , B_2O_3 , Al_2O_3 , Fe_2O_3 , ZrO_2 , Na_2O , Li_2O , CaO , MgO , and Others) used in CVS-I. With the possible exception of the "Others" component, all components appear to have a significant effect on at least one property of interest.
- Reduce the size of the CVS-II composition region from that studied in CVS-I to eliminate compositions with properties far removed from acceptable values. The region should contain compositions with properties somewhat outside of acceptable limits, but not too far outside. Specific recommendations are to 1) reduce the upper limit on the sum of the mass fractions of Fe_2O_3 , Al_2O_3 , ZrO_2 , and Others to 0.22, and 2) apply an upper limit of 0.19 to the sum of the mass fractions of MgO , CaO , and ZrO_2 .
- Include both exterior and interior compositions of the CVS-II region in CVS-II test matrices. Exterior compositions reduce uncertainty in fitted empirical models and ensure that the model can differentiate between glasses with acceptable and unacceptable properties. Interior compositions ensure that the models accurately reflect the behavior of glass properties over the whole region of interest.
- Include a representative standard glass with all testing, property measurement, and analytical work. If the glass does not have certified values and corresponding uncertainties for all properties of interest, this should be accomplished if possible. This will permit detection and elimination of biases and/or erroneous data.
- Modify the way in which glasses are assigned to "batches" for the MCC-1 and PCT leach tests when there are too many samples to test at once. During CVS-I, duplicate leach tests of approximately half of the glasses were begun at one time, with the other half begun at a later time. This confounds variations over time with compositional effects, which should be avoided. In CVS-II, the duplicate MCC-1 and PCT leach tests will be performed in two batches such that one complete set is done in one batch, and one complete set is done in a second batch. This has the advantages of 1) not confounding time effects with composition effects, and 2) picking up longer-term variation as well as shorter-term variation in duplicate results.

- Include a few compositions in CVS-II with "Others" mixes corresponding to NCRW, PFP, and CC wastes. CVS-I results suggest that the "Others" component with a mix corresponding to NCAW has little effect on glass properties, and it is necessary to investigate this for the other waste types.
- Investigate the development of liquidus temperature models by other than the empirical mixture model approach envisioned for the other glass properties. Liquidus temperature is a complex function of composition, and the empirical mixture modeling approach is not anticipated to be sufficient for the whole set of CVS liquidus temperature data. The empirical modeling approach may be useful if applied to subsets of data corresponding to specific crystalline phases. Provided adequate liquidus temperature models can be developed, constraints based on such models should replace some of all of the ad-hoc multiple-component constraints used in CVS-I and CVS-II.

7.2.2 Recommendations on Use of CVS-I Results

The CVS-I fitted linear mixture models can be used for the following purposes provided the results are considered as very preliminary and subject to considerable uncertainty:

- Development of the CVS-II composition region and CVS-II test matrices.
- Formulation of radioactive test glasses to assist in the development and evaluation of HWVP waste streams.
- Development of glass/frit compositions for radioactive core samples.
- Development of the HWVP feed specification and determination of the maximum waste loading.

CVS-I data falling outside of the ultimate CVS-II composition region may not be able to be combined with CVS-II data to develop updated empirical mixture models, but can still be used to augment CVS-II data in certain ways.

8.0 REFERENCES

- Babcock, C. L. 1977. Silicate Glass Technology Methods. John Wiley & Sons, New York.
- Bickford, D. F., and C. M. Jantzen. 1984. "Devitrification Behavior of SRP Defense Waste Glass." In Material Research Society Symposium Proceedings 26:557-566.
- Bickford, D. F., and C. M. Jantzen. 1986. "Devitrification of Defense Nuclear Waste Glasses." Journal of Non-Crystalline Solids 84:299-307.
- Box, G.E.P., and N. R. Draper. 1987. Empirical Model Building and Response Surfaces. John Wiley and Sons, New York.
- Chick, L. A., and G. F. Piepel. 1984. "Statistically Designed Optimization of a Glass Composition." Journal of the American Ceramic Society 67(11):763-768.
- Chick, L. A., J. L. Swanson, and D. S. Goldman. 1984. "Nuclear Waste Glass Composition Limitations." Proceedings of Fuel Reprocessing and Waste Management, Vol. 1. American Nuclear Society, Inc., LaGrange Park, Illinois.
- Cornell, J. A. 1990. Experiments with Mixtures: Design, Models, and the Analysis of Mixture Data. 2nd ed. John Wiley and Sons, New York.
- Draper, N. R., and H. Smith. 1981. Applied Regression Analysis. 2nd ed. John Wiley and Sons, New York.
- Goles, R. W., and R. K. Nakaoka. 1988. Hanford Waste Vitrification Program Pilot-Scale Melter Test Number 23 Summary Report. PNL-7142, Pacific Northwest Laboratory, Richland, Washington.
- Hagy, H. E., et al. 1974. "Physical Properties of Glass." Chapter 17 in The Handbook of Glass Manufacture, ed. F. V. Tooley, pp. 933-937, Books For Industry, Inc., New York.
- Jantzen, C. M. 1988. "Prediction of Glass Durability as a Function of Glass Composition and Test Conditions: Thermodynamics and Kinetics." Proceedings of the First International Conference on Advances in the Fusion of Glass, pp. 24.1-24.17. American Ceramic Society, Westerville, Ohio.
- Jantzen, C. M., and D. F. Bickford. 1985. "Leaching of Devitrified Glass Containing Simulated SRP Nuclear Waste." Material Research Society Symposium Proceedings 44:135-146.
- Kruger, O. L. 1990. Hanford Waste Vitrification Plant Applied Technology Plan. WHC-EP-0350, Westinghouse Hanford Company, Richland, Washington.

MCC-1 STATIC LEACH TEST METHOD. 1983. Materials Characterization Center, Pacific Northwest Laboratory, Richland, Washington.

Nelson, J. L. 1988. Preliminary Hanford Waste Vitrification Plant Waste Form Qualification Plan - FY 1988 Update. WHC-EP-0045, Westinghouse Hanford Company, Richland, Washington.

Pederson, L. R., D. R. Baer, G. L. McVay, and M. H. Engelhard. 1986. "Reaction of Soda Lime Silicate Glass in Isotopically Labelled Water." Journal of Non-Crystalline Solids 86:369-380.

Pelton, A. D., and G. Eriksson. 1988. "A Thermodynamic Database Computing System for Multicomponent Glasses." Advances in the Fusion of Glass. The American Ceramic Society, Westerville, Ohio.

Piepel, G. F. 1982. "Measuring Component Effects in Constrained Mixture Experiments." Technometrics 24:29-39.

Piepel, G. F. 1988. "Programs for Generating Extreme Vertices and Centroids of Linearly Constrained Experimental Regions." Journal of Quality Technology 20:125-139.

Piepel, G. F. 1989. MIXSOFT and MIXSOFT User's Guide, Version 1.0. MIXSOFT--Mixture Experiment Software, Richland, Washington.

Piepel, G. F., G. B. Mellinger, and M. A. Reimus. 1989. "A Statistical Approach for Characterizing Chemical Durability Within A Waste Glass Compositional Region." Waste Management 9:3-11.

SAS Institute Inc. 1985a. SAS User's Guide: Statistics, Version 5 Edition. SAS Institute Inc., Cary, NC.

SAS Institute Inc. 1985b. SAS/GRAPH User's Guide, Version 5 Edition. SAS Institute Inc., Cary, NC.

SAS Institute Inc. 1990. SAS/STAT User's Guide, Version 6, Fourth Edition. SAS Institute Inc., Cary, NC.

Sexton, R. A. 1988. Hanford Waste Vitrification Plant Technology Plan. WHC-EP-0139, Westinghouse Hanford Company, Richland, Washington.

Shelby, J. E. 1983. "Properties/Morphology Relations in Alkali Silicate Glasses." Journal of the American Ceramic Society 66:754.

Strachan, D. M. 1983. "Effect of Gamma Irradiation on Simulated Waste Glass Leaching and on the Leach Vessel." Journal of the American Ceramic Society 66:158-160.

Strachan, D. M., R. P. Turcotte, and B. O. Barnes. 1982. "MCC-1: A Standard Leach Test for Nuclear Waste Forms." Nuclear Technology 56[2]:306-312.

Tomozawa, M. 1979. "Phase Separation in Glass." Glass II (Edited by M. Tomozawa and R. H. Doremus), Academic Press, New York.

U.S. Department of Energy. 1982. Environmental Assessment-Waste Form Selection for SRP High-Level Waste. USDOE Report DOE/EA 0179, Washington, D.C.

U.S. Department of Energy. 1990. Quality Assurance Requirements Document. DOE/RW-0214, Office of Civilian Radioactive Waste Management, U.S. Department of Energy, Washington, D.C.

Welch, W. J. 1987. ACED, Algorithms for the Construction of Experimental Design, User's Guide Version 1.6.1. University of Waterloo, Waterloo, Ontario, Canada.

APPENDIX A

COMPARISON OF TARGET AND ANALYZED COMPOSITIONS FOR CVS-I GLASSES
AND LONGER-TERM UNCERTAINTY IN ANALYZED COMPOSITIONS

APPENDIX A

COMPARISON OF TARGET AND ANALYZED COMPOSITIONS FOR CVS-I GLASSES AND LONGER-TERM UNCERTAINTY IN ANALYZED COMPOSITIONS

As part of the CVS-I experimental work, each of the 23 CVS-I glasses was submitted for chemical analysis by ICP. Table A.1 lists the analyzed and target compositions. The target compositions were obtained by starting with the 10 component compositions listed in Table 4.6 and expanding the "Others" component into its constituents according to Table 4.4. In most cases, the analyzed component values are the averages of two ICP results from K/Ni and Na/Zr fusions, although in some cases only one of these two results was available or used. Note that target composition values were inserted in place of analyzed values when minor components were not detected analytically. This was done to enable checking how close the sums of the analyzed values were to 100 wt%. The following observations are made based on Table A.1:

- K_2O and TiO_2 , and in some cases Al_2O_3 , CaO , and ZrO_2 , were detected in glasses that did not (or at least were not supposed to) contain these components.
- SiO_2 analyzed values were lower than target values for most of the 23 CVS-I glasses, sometimes up to 3 wt% low.
- Glasses 7, 8, 14, 18, and 22 (a replicate of #8) had analyzed values of ZrO_2 noticeably lower than the corresponding target values. Most of these differences were around 1 wt%, but the difference was over 3 wt% for #18.

The results in the first two bullets appear to be due to biases in the analytic process. The under-analysis of ZrO_2 in some glasses may be related to the presence of undissolved ZrO_2 or Zr-containing crystals that segregated from the bulk of the melt.

Table A.2 lists the summary statistics for the differences between the analyzed and target values for each oxide component. Differences for a number of components were statistically significant (based on a two-sided t-test at

the 90% confidence level), although several of these may be due to "round-off" errors or be too small to be of practical consequence. The main observation is:

- Glass components with statistically significant mass fraction differences greater than 0.0010 (0.10 wt%) include B_2O_3 , LiO_2 , Na_2O , Nd_2O_3 , SiO_2 , and ZrO_2 . All except B_2O_3 have analyzed values that tend to be lower than the target values. B_2O_3 tends to be too high.

It is not clear whether any of these differences are "real" composition differences (e.g., due to volatilization or batching errors) or whether they are analytical biases. The fact that the total of analyzed components was less than 100 wt% (1.0 for mass fractions) for most of the glasses, suggests that analytical biases are involved. A "black glass" with composition close to that of HW-39-4 will be included in all future CVS work in order to help address the bias issue (for property testing as well as composition analyses).

Table A.3 gives the target and analytical compositions for six replicate analyses of glass #19 conducted over three months. Glass #19 is a replicate of glass #1, the center point of the CVS-I composition region. The main observations from Table A.3 are:

- K_2O and TiO_2 were detected for some analyses, although these components are not nominally in #19.
- SiO_2 was approximately 1.0 wt% low for four of the six analyses.

These results indicate that if indeed the differences seen over the set of 23 CVS-I glasses are due to biases in the analytical process, then they continued over a three-month period.

Table A.4 gives the means, standard deviations (SD), and percent relative standard deviations (%RSD) of the oxide components based on the six replicate analyses of CVS1-19. The SDs and %RSDs give an indication of the long-term within-lab variation (precision) in analyses that might be expected. The %RSDs tend to be under 5% for components present at more than very minor concentrations, which agrees well with past experience. However, based on the above results, analytical bias more than imprecision may be the most important issue.

TABLE A.1. Target (T) and Analyzed (A) Compositions (in mass fractions) for CVS-I Glasses

Oxide	CVS1-1		CVS1-2		CVS1-3		CVS1-4		CVS1-5	
	T	A	T	A	T	A	T	A	T	A
Al ₂ O ₃	0.0636	0.0642	0.1500	0.1500	0.1400	0.1380	0.0000	0.0000 ^(a)	0.0800	0.0803
B ₂ O ₃	0.1142	0.1160	0.0500	0.0511	0.2000	0.2010	0.2000	0.2000	0.0500	0.0517
BaO	0.0007	0.00073	0.0002	0.00019 ^(b)	0.0002	0.00018	0.0002	0.00018	0.0002	0.00019
CaO	0.0275	0.0277	0.1000	0.1020	0.0000	0.00043	0.0200	0.0204	0.0000	0.00104
CdO	0.0055	0.00554	0.0013	0.00138	0.0013	0.00136	0.0013	0.00140	0.0013	0.00134
CeO ₂	0.0011	0.0012	0.0003	0.0003 ^(a)	0.0003	0.0007	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)
Cr ₂ O ₃	0.0009	0.0010	0.0002	0.0002 ^(a)	0.0002	0.0003	0.0002	0.0003	0.0002	0.0000 ^(a)
Cs ₂ O	0.0011	0.0010	0.0003	0.00025	0.0003	0.00022	0.0003	0.00026	0.0003	0.00024
CuO	0.0011	0.00111	0.0003	0.00028	0.0003	0.00029	0.0003	0.00031	0.0003	0.00030
F	0.0022	0.0022 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)
Fe ₂ O ₃	0.0568	0.0566	0.0200	0.0203	0.0200	0.0202	0.0200	0.0210	0.1500	0.1490
K ₂ O	0.0000	0.0080	0.0000	0.0040	0.0000	0.0090	0.0000	0.0050	0.0000	0.0090
La ₂ O ₃	0.0046	0.00441	0.0011	0.00119	0.0011	0.00116	0.0011	0.00113	0.0011	0.00109
Li ₂ O	0.0376	0.0340	0.0700	0.0615	0.0700	0.0601	0.0100	0.00860	0.0700	0.0620
MgO	0.0363	0.0359	0.0000	0.0000 ^(a)	0.0800	0.0776	0.0800	0.0791	0.0000	0.0000 ^(a)
MnO ₂	0.0011	0.00117	0.0003	0.00032	0.0003	0.00033	0.0003	0.00038	0.0003	0.00037
MoO ₃	0.0022	0.00220	0.0005	0.00051	0.0005	0.00054	0.0005	0.00055	0.0005	0.00056
Na ₂ O	0.1003	0.0891	0.0500	0.0504	0.0500	0.0511	0.0900	0.0893	0.0700	0.0641
Nd ₂ O ₃	0.0090	0.00832	0.0022	0.00207	0.0022	0.00215	0.0022	0.00205	0.0022	0.00205
NiO	0.0042	0.00443	0.0010	0.00128	0.0010	0.00141	0.0010	0.00136	0.0010	0.00135
P ₂ O ₅	0.0007	0.0007 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)
PdO	0.0004	0.0004 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)
Pr ₆ O ₁₁	0.0007	0.0007 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)
Rb ₂ O	0.0004	0.0004 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)
Rh ₂ O ₃	0.0004	0.0004 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)
RuO ₂	0.0011	0.0011 ^(a)	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)
SO ₃	0.0020	0.0020 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)
SiO ₂	0.4801	0.4770	0.5500	0.5200	0.4200	0.4110	0.5700	0.5460	0.5700	0.5630
Sm ₂ O ₃	0.0004	0.0004 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)
SrO	0.0007	0.00076	0.0002	0.00024	0.0002	0.00019	0.0002	0.00020	0.0002	0.00021
TiO ₂	0.0000	0.00016	0.0000	0.0000 ^(a)	0.0000	0.00012	0.0000	0.0000 ^(a)	0.0000	0.00012
Y ₂ O ₃	0.0004	0.00037	0.0001	0.00010	0.0001	0.00010	0.0001	0.00011	0.0001	0.00010
ZrO ₂	<u>0.0429</u>	<u>0.0418</u>	<u>0.0000</u>	<u>0.00896</u>	<u>0.0100</u>	<u>0.00896</u>	<u>0.0000</u>	<u>0.00049</u>	<u>0.0000</u>	<u>0.00020</u>
Sum	1.000	0.9910	1.000	0.9787	1.000	0.9885	1.000	0.9806	1.000	0.9907

(a) Below analytical detection limit or not analyzed--target value assumed.

(b) Value from ICP with K/Ni fusion--the value for Na/Zr fusion (.00082) was too high)

TABLE A.1. (contd)

Oxide	CVS1-6		CVS1-7		CVS1-8		CVS1-9		CVS1-10	
	T	A	T	A	T	A	T	A	T	A
Al ₂ O ₃	0.0000	0.00087	0.0000	0.00096	0.0000	0.00090	0.0000	0.0000 ^(a)	0.1200	0.1210
B ₂ O ₃	0.2000	0.1920	0.0500	0.0507	0.0500	0.0527	0.1962	0.2020	0.0851	0.0848
BaO	0.0018	0.00164	0.0002	0.00019	0.0002	0.00019	0.0018	0.00176	0.0018	0.00175
CaO	0.0000	0.00117	0.1000	0.1000	0.0000	0.00027	0.0000	0.00037	0.0000	0.00047
CdO	0.0134	0.0130	0.0013	0.00139	0.0013	0.00143	0.0134	0.0141	0.0134	0.0118
CeO ₂	0.0027	0.0027	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0027	0.0030	0.0027	0.0030
Cr ₂ O ₃	0.0022	0.0022	0.0002	0.0002 ^(a)	0.0002	0.0003	0.0022	0.0022	0.0022	0.0024
Cs ₂ O	0.0027	0.0025	0.0003	0.00026	0.0003	0.00028	0.0027	0.0025	0.0027	0.0024
CuO	0.0027	0.00254	0.0003	0.00029	0.0003	0.00033	0.0027	0.00268	0.0027	0.00268
F	0.0054	0.0054 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0054	0.0054 ^(a)	0.0054	0.0054 ^(a)
Fe ₂ O ₃	0.0200	0.0190	0.0336	0.0334	0.1500	0.1520	0.1400	0.1400	0.0200	0.0206
K ₂ O	0.0000	0.0070	0.0000	0.0070	0.0000	0.0060	0.0000	0.0000	0.0000	0.0050
La ₂ O ₃	0.0112	0.0100	0.0011	0.00123	0.0011	0.00114	0.0112	0.0111	0.0112	0.0112
Li ₂ O	0.0700	0.0616	0.0100	0.00871	0.0100	0.00921	0.0100	0.00909	0.0100	0.00873
MgO	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0800	0.0807	0.0800	0.0816	0.0000	0.0000 ^(a)
MnO ₂	0.0027	0.00271	0.0003	0.00031	0.0003	0.00037	0.0027	0.00289	0.0027	0.00281
MoO ₃	0.0054	0.00504	0.0005	0.00053	0.0005	0.00061	0.0054	0.00547	0.0054	0.00514
Na ₂ O	0.0500	0.0537	0.0964	0.0946	0.0837	0.0780	0.0538	0.0532	0.0949	0.0924
Nd ₂ O ₃	0.0221	0.0188	0.0022	0.00212	0.0022	0.00212	0.0221	0.0201	0.0221	0.0201
NiO	0.0103	0.00942	0.0010	0.00136	0.0010	0.00151	0.0103	0.0106	0.0103	0.0105
P ₂ O ₅	0.0018	0.0018 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)	0.0018	0.0018 ^(a)
PdO	0.0009	0.0009 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0009	0.0009 ^(a)
Pr ₆ O ₁₁	0.0018	0.0018 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)	0.0018	0.0018 ^(a)
Rb ₂ O	0.0009	0.0009 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0009	0.0009 ^(a)
Rh ₂ O ₃	0.0009	0.0009 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0009	0.0009 ^(a)
RuO ₂	0.0027	0.0025	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0027	0.0024	0.0027	0.0020
SO ₃	0.0049	0.0049 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0049	0.0049 ^(a)	0.0049	0.0049 ^(a)
SiO ₂	0.4400	0.4150	0.5700	0.5550	0.5363	0.5450	0.4200	0.4140	0.5700	0.5650
Sm ₂ O ₃	0.0009	0.0009 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0009	0.0009 ^(a)
SrO	0.0018	0.00168	0.0002	0.00024	0.0002	0.00022	0.0018	0.00180	0.0018	0.00179
TiO ₂	0.0000	0.00031	0.0000	0.00032	0.0000	0.00022	0.0000	0.0000 ^(a)	0.0000	0.00013
Y ₂ O ₃	0.0009	0.00087	0.0001	0.00012	0.0001	0.00011	0.0009	0.00097	0.0009	0.00100
ZrO ₂	<u>0.1200</u>	<u>0.1160</u>	<u>0.1300</u>	<u>0.1220</u>	<u>0.0800</u>	<u>0.0696</u>	<u>0.0000</u>	<u>0.00020</u>	<u>0.0000</u>	<u>0.00017</u>
Sum	1.000	0.9598	1.000	0.9833	1.000	1.0056	1.000	1.0025	1.000	0.9944

(a) Below analytical detection limit or not analyzed--target value assumed.

TABLE A.1. (contd)

Oxide	CVS1-11		CVS1-12		CVS1-13		CVS1-14		CVS1-15	
	T	A	T	A	T	A	T	A	T	A
Al ₂ O ₃	0.1400	0.1450	0.0000	0.0000 ^(a)	0.0038	0.00432	0.0238	0.0240	0.0000	0.0000 ^(a)
B ₂ O ₃	0.1549	0.1600	0.1764	0.1810	0.2000	0.2030	0.2000	0.1960	0.0500	0.0507
BaO	0.0014	0.00143	0.0002	0.00021	0.0002	0.00018	0.0002	0.00017	0.0018	0.00169
CaO	0.1000	0.1030	0.1000	0.1020	0.0000	0.00029	0.0000	0.00015	0.0000	0.00047
CdO	0.0107	0.0110	0.0013	0.00142	0.0013	0.00137	0.0013	0.00132	0.0134	0.0136
CeO ₂	0.0022	0.0023	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0027	0.0033
Cr ₂ O ₃	0.0018	0.0019	0.0002	0.0003	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0022	0.0023
Cs ₂ O	0.0022	0.0020	0.0003	0.00023	0.0003	0.00026	0.0003	0.00024	0.0027	0.0026
CuO	0.0022	0.00229	0.0003	0.00033	0.0003	0.00030	0.0003	0.00029	0.0027	0.00252
F	0.0043	0.0043 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0054	0.0054 ^(a)
Fe ₂ O ₃	0.0200	0.0206	0.1500	0.1490	0.0200	0.0205	0.0200	0.0194	0.0200	0.0201
K ₂ O	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.0060	0.0000	0.0100
La ₂ O ₃	0.0090	0.00896	0.0011	0.00119	0.0011	0.00113	0.0011	0.00109	0.0112	0.0105
Li ₂ O	0.0100	0.00982	0.0700	0.0703	0.0100	0.00856	0.0100	0.00925	0.0700	0.0568
MgO	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0800	0.0760
MnO ₂	0.0022	0.00233	0.0003	0.00037	0.0003	0.00033	0.0003	0.00031	0.0027	0.00282
MoO ₃	0.0043	0.00434	0.0005	0.00051	0.0005	0.00056	0.0005	0.00052	0.0054	0.00527
Na ₂ O	0.0751	0.0730	0.0736	0.0761	0.1862	0.1740	0.1862	0.1850	0.1211	0.1120
Nd ₂ O ₃	0.0177	0.0163	0.0022	0.00204	0.0022	0.00197	0.0022	0.00202	0.0221	0.0131
NiO	0.0082	0.00843	0.0010	0.00144	0.0010	0.00133	0.0010	0.00125	0.0103	0.0101
P ₂ O ₅	0.0014	0.0014 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)
PdO	0.0007	0.0007 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)
Pr ₆ O ₁₁	0.0014	0.0014 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)
Rb ₂ O	0.0007	0.0007 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)
Rh ₂ O ₃	0.0007	0.0007 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)
RuO ₂	0.0022	0.0021	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0027	0.0021
SO ₃	0.0039	0.0039 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0049	0.0049 ^(a)
SiO ₂	0.4200	0.4180	0.4200	0.4170	0.5700	0.5510	0.4200	0.4040	0.5589	0.5380
Sm ₂ O ₃	0.0007	0.0007 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)
SrO	0.0014	0.00150	0.0002	0.00025	0.0002	0.00021	0.0002	0.00018	0.0018	0.00170
TiO ₂	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.00025	0.0000	0.00012
Y ₂ O ₃	0.0007	0.00077	0.0001	0.00014	0.0001	0.00010	0.0001	0.00010	0.0009	0.00091
ZrO ₂	<u>0.0000</u>	<u>0.00020</u>	<u>0.0000</u>	<u>0.00013</u>	<u>0.0000</u>	<u>0.00058</u>	<u>0.1300</u>	<u>0.1230</u>	<u>0.0000</u>	<u>0.00022</u>
Sum	1.000	1.0091	1.000	1.0064	1.000	0.9726	1.000	0.9771	1.000	0.9544

(a) Below analytical detection limit or not analyzed--target value assumed.

TABLE A.1. (contd)

Oxide	CVS1-16		CVS1-17		CVS1-18		CVS1-19		CVS1-20	
	T	A	T	A	T	A	T	A	T	A
Al ₂ O ₃	0.1442	0.1430	0.0000	0.0000 ^(a)	0.0000	0.00089	0.0636	0.0636	0.0636	0.0637
B ₂ O ₃	0.0500	0.0509	0.0500	0.0513	0.0500	0.0516	0.1142	0.1150	0.1142	0.1160
BaO	0.0002	0.00017	0.0018	0.00172	0.0016	0.00156	0.0007	0.00071	0.0007	0.00071
CaO	0.0000	0.00044	0.1000	0.0995	0.0200	0.0220	0.0275	0.0289	0.0275	0.0270
CdO	0.0013	0.00141	0.0134	0.0136	0.0121	0.0126	0.0055	0.00565	0.0055	0.00550
CeO ₂	0.0003	0.0003 ^(a)	0.0027	0.0029	0.0024	0.0026	0.0011	0.0014	0.0011	0.0012
Cr ₂ O ₃	0.0002	0.0002 ^(a)	0.0022	0.0023	0.0020	0.0022	0.0009	0.0010	0.0009	0.0010
Cs ₂ O	0.0003	0.00025	0.0027	0.0026	0.0024	0.0022	0.0011	0.0010	0.0011	0.0011
CuO	0.0003	0.00028	0.0027	0.00260	0.0024	0.00239	0.0011	0.00109	0.0011	0.00112
F	0.0005	0.0005 ^(a)	0.0054	0.0054 ^(a)	0.0048	0.0048 ^(a)	0.0022	0.0022 ^(a)	0.0022	0.0022 ^(a)
Fe ₂ O ₃	0.0858	0.0851	0.1400	0.1370	0.0200	0.0202	0.0568	0.0559	0.0568	0.0555
K ₂ O	0.0000	0.0070	0.0000	0.0040	0.0000	0.0130	0.0000	0.0080	0.0000	0.0140
La ₂ O ₃	0.0011	0.00114	0.0112	0.0108	0.0101	0.00972	0.0046	0.00436	0.0046	0.00433
Li ₂ O	0.0100	0.00851	0.0100	0.00910	0.0700	0.0616	0.0376	0.0345	0.0376	0.0350
MgO	0.0800	0.0771	0.0000	0.0000 ^(a)	0.0800	0.0754	0.0363	0.0355	0.0363	0.0344
MnO ₂	0.0003	0.00035	0.0027	0.00285	0.0024	0.00248	0.0011	0.00118	0.0011	0.00112
MoO ₃	0.0005	0.00053	0.0054	0.00528	0.0048	0.00491	0.0022	0.00220	0.0022	0.00217
Na ₂ O	0.1873	0.1740	0.1455	0.1540	0.1186	0.1150	0.1003	0.0964	0.1003	0.1100
Nd ₂ O ₃	0.0022	0.00207	0.022	0.0195	0.0199	0.0179	0.0090	0.00810	0.0090	0.00808
NiO	0.0010	0.00136	0.0103	0.0104	0.0093	0.00930	0.0042	0.00433	0.0042	0.00443
P ₂ O ₅	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)	0.0016	0.0016 ^(a)	0.0007	0.0007 ^(a)	0.0007	0.0007 ^(a)
PdO	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0008	0.0008 ^(a)	0.0004	0.0004 ^(a)	0.0004	0.0004 ^(a)
Pr ₆ O ₁₁	0.0002	0.0002 ^(a)	0.0018	0.0018 ^(a)	0.0016	0.0016 ^(a)	0.0007	0.0007 ^(a)	0.0007	0.0007 ^(a)
Rb ₂ O	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0008	0.0008 ^(a)	0.0004	0.0004 ^(a)	0.0004	0.0004 ^(a)
Rh ₂ O ₃	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0008	0.0008 ^(a)	0.0004	0.0004 ^(a)	0.0004	0.0004 ^(a)
RuO ₂	0.0003	0.0003 ^(a)	0.0027	0.0021	0.0024	0.0021	0.0011	0.0016	0.0011	0.0013
SO ₃	0.0005	0.0005 ^(a)	0.0049	0.0049 ^(a)	0.0044	0.0044 ^(a)	0.0020	0.0020 ^(a)	0.0020	0.0020 ^(a)
SiO ₂	0.4327	0.4230	0.4545	0.4380	0.4214	0.4190	0.4801	0.4760	0.4801	0.4750
Sm ₂ O ₃	0.0001	0.0001 ^(a)	0.0009	0.0009 ^(a)	0.0008	0.0008 ^(a)	0.0004	0.0004 ^(a)	0.0004	0.0004 ^(a)
SrO	0.0002	0.00019	0.0018	0.00179	0.0016	0.00163	0.0007	0.00074	0.0007	0.00074
TiO ₂	0.0000	0.0000 ^(a)	0.0000	0.0000 ^(a)	0.0000	0.00028	0.0000	0.00017	0.0000	0.00016
Y ₂ O ₃	0.0001	0.00011	0.0009	0.00092	0.0008	0.00083	0.0004	0.00037	0.0004	0.00037
ZrO ₂	<u>0.0000</u>	<u>0.00016</u>	<u>0.0000</u>	<u>0.00037</u>	<u>0.1300</u>	<u>0.0975</u>	<u>0.0429</u>	<u>0.0400</u>	<u>0.0429</u>	<u>0.0411</u>
Sum	1.000	0.9797	1.000	0.9901	1.000	0.9645	1.000	0.9949	1.000	1.0122

(a) Below analytical detection limit or not analyzed--target value assumed.

TABLE A.1. (contd)

Oxide	CVS1-21		CVS1-22		CVS1-23	
	T	A	T	A	T	A
Al ₂ O ₃	0.0000	0.0074	0.0000	0.00081	0.0456	0.0434
B ₂ O ₃	0.2000	0.2010	0.0500	0.0512	0.0956	0.0945
BaO	0.0002	0.00019	0.0002	0.00019	0.0007	0.00066
CaO	0.0200	0.0214	0.0000	0.00088	0.0289	0.0294
CdO	0.0013	0.00137	0.0013	0.00138	0.0053	0.00517
CeO ₂	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0011	0.0011
Cr ₂ O ₃	0.0002	0.00035	0.0002	0.0002 ^(a)	0.0009	0.0009
Cs ₂ O	0.0003	0.00025	0.0003	0.00025	0.0011	0.0010
CuO	0.0003	0.00031	0.0003	0.00058	0.0011	0.00102
F	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0021	0.0021 ^(a)
Fe ₂ O ₃	0.0200	0.0207	0.1500	0.1480	0.1179	0.1140
K ₂ O	0.0000	0.0000 ^(a)	0.0000	0.0070	0.0000	0.0090
La ₂ O ₃	0.0011	0.00126	0.0011	0.00108	0.0044	0.00413
Li ₂ O	0.0100	0.00858	0.0100	0.00955	0.0375	0.0296
MgO	0.0800	0.0795	0.0800	0.0754	0.0084	0.0078
MnO ₂	0.0003	0.00037	0.0003	0.00033	0.0011	0.00115
MoO ₃	0.0005	0.00056	0.0005	0.00052	0.0021	0.00210
Na ₂ O	0.0800	0.0855	0.0837	0.0836	0.1052	0.0943
Nd ₂ O ₃	0.0022	0.00205	0.0022	0.00204	0.0087	0.00761
NiO	0.0010	0.00140	0.0010	0.00177	0.0040	0.00399
P ₂ O ₅	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0007	0.0007 ^(a)
PdO	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0004	0.0004 ^(a)
Pr ₆ O ₁₁	0.0002	0.0002 ^(a)	0.0002	0.0002 ^(a)	0.0007	0.0007 ^(a)
Rb ₂ O	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0004	0.0004 ^(a)
Rh ₂ O ₃	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0004	0.0004 ^(a)
RuO ₂	0.0003	0.0003 ^(a)	0.0003	0.0003 ^(a)	0.0011	0.0011 ^(a)
SO ₃	0.0005	0.0005 ^(a)	0.0005	0.0005 ^(a)	0.0019	0.0019 ^(a)
SiO ₂	0.5700	0.5540	0.5363	0.5340	0.5153	0.5140 ^(b)
Sm ₂ O ₃	0.0001	0.0001 ^(a)	0.0001	0.0001 ^(a)	0.0004	0.0004 ^(a)
SrO	0.0002	0.00023	0.0002	0.00020	0.0007	0.00070
TiO ₂	0.0000	0.0000 ^(a)	0.0000	0.00022	0.0000	0.00011
Y ₂ O ₃	0.0001	0.00011	0.0001	0.00011	0.0004	0.00036
ZrO ₂	<u>0.0000</u>	<u>0.00022</u>	<u>0.0800</u>	<u>0.0703</u>	<u>0.0063</u>	<u>0.00640</u>
Sum	1.000	0.9892	1.000	0.9920	1.000	0.9805

(a) Below analytical detection limit or not analyzed--target value assumed.

(b) Value from ICP with K/Ni fusion--value for Na/Zr fusion (.4570) was too low.

TABLE A.2. Summary Statistics for Differences Between Analyzed and Target Values for Each Component Based on the 23 CVS-I Glasses

Oxide	Analyzed - Target Differences(a)				Significantly Different at 90% Confidence Level
	Mean	SD	SE	t	
Al ₂ O ₃	0.00062	0.001989	0.00041475	1.48	
B ₂ O ₃	0.00102	0.002823	0.00058858	1.73	x
BaO	-0.00003	0.000043	0.00000899	-2.95	x ^(b)
CaO	0.00078	0.000862	0.00017966	4.33	x ^(c)
CdO	0.00004	0.000411	0.00008578	0.47	
Ce ₂ O ₃	0.00011	0.000166	0.00003461	3.27	x ^(c)
Cr ₂ O ₃	0.00006	0.000086	0.00001796	3.27	x ^(b)
Cs ₂ O	-0.00010	0.000074	0.00001549	-6.20	x ^(c)
CuO	-0.00001	0.000086	0.00001802	-0.41	
F	0.00000	0.000000	0.00000000	--	
Fe ₂ O ₃	-0.00042	0.001302	0.00027141	-1.54	
K ₂ O	0.00600	0.004034	0.00084114	7.13	x ^(d)
La ₂ O ₃	-0.00014	0.000311	0.00006488	-2.10	x ^(c)
Li ₂ O	-0.00372	0.003917	0.00081676	-4.56	x
MgO	-0.00093	0.001674	0.00034904	-2.65	x ^(c)
MnO ₂	0.00007	0.000048	0.00000994	6.78	x ^(b)
MoO ₃	-0.00001	0.000112	0.00002337	-0.33	
Na ₂ O	-0.00263	0.006102	0.00127235	-2.06	x
Nd ₂ O ₃	-0.00120	0.001945	0.00040548	-2.95	x
NiO	0.00022	0.000310	0.00006462	3.47	x ^(c)
P ₂ O ₅	0.00000	0.000000	0.00000000	--	
PdO	0.00000	0.000000	0.00000000	--	
Pr ₆ O ₁₁	0.00000	0.000000	0.00000000	--	
Rb ₂ O	0.00000	0.000000	0.00000000	--	
Rh ₂ O ₃	0.00000	0.000000	0.00000000	--	
RuO ₂	-0.00009	0.000264	0.00005514	-1.66	

TABLE A.2. (contd)

Oxide	Analyzed - Target Differences(a)				Significantly Different at 90% Confidence Level
	Mean	SD	SE	t	
SO ₃	0.00000	0.000000	0.00000000	--	
SiO ₂	-0.01016	0.009469	0.00197435	-5.15	x
Sm ₂ O ₃	0.00000	0.000000	0.00000000	--	
SrO	0.00001	0.000047	0.00000979	0.84	
TiO ₂	0.00012	0.000112	0.00002327	5.03	x ^(c)
Y ₂ O ₃	0.00001	0.000034	0.00000719	1.51	
ZrO ₂	-0.00289	0.007660	0.00159719	-1.87	x

(a) SD = standard deviation; %RSD = percent relative standard deviation;
SE = standard error (SD/ $\sqrt{23}$); t = t-statistic (Mean/SE)

(b) Average difference from target is less than 0.0001 (0.01 wt%), and may be due to the specification of target values to four decimal places. Although statistically significant, the difference may not be real, and probably isn't of practical significance.

(c) Average difference from target is less than 0.001 (0.1 wt%), and may not be of practical significance.

(d) Not contained in CVS-I glasses.

TABLE A.3. Target (T) and Analyzed (A) Compositions (in mass fractions)
for Six Replicate Analyses of CVS-I Glass CVS1-19 Conducted
Over Three Months

		Replicate Analyses and Dates					
K/Ni Fusion Na/Zr Fusion		4/20/89	4/15/89	5/17/89	6/30/89	6/30/89	7/25/89
		4/21/89	4/20/89	5/17/89	6/30/89	6/30/89	7/25/89
Oxide	Target	19-1	19-2	19-3	19-4	19-5	19-6
Al ₂ O ₃	0.0636	0.0636	0.0630	0.0668	0.0626	0.0630	0.0637
B ₂ O ₃	0.1142	0.1150	0.1140	0.1200	0.1140	0.1140	0.1170
BaO	0.0007	0.00071	0.00070	0.00073	0.00071	0.00071	0.00070
CaO	0.0275	0.0289	0.0275	0.0288	0.0277	0.0290	0.0273
CdO	0.0055	0.00565	0.00558	0.00564	0.00532	0.00536	0.00532
CeO ₂	0.0011	0.0014	0.0013	0.0011 ^(a)	0.0012	0.0011	0.00116
Cr ₂ O ₃	0.0009	0.00095	0.0010	0.00102	0.00100	0.00099	0.00091
Cs ₂ O	0.0011	0.0010	0.0010	0.0012	0.0012	0.0012	0.0010
CuO	0.0011	0.00109	0.00103	0.00112	0.00110	0.00108	0.00108
F	0.0022	0.0022 ^(a)	0.0022 ^(a)	0.0022 ^(a)	0.0022 ^(a)	0.0022 ^(a)	0.0022 ^(a)
Fe ₂ O ₃	0.0568	0.0559	0.0548	0.0558	0.0544	0.0548	0.0542
K ₂ O	0.0000	0.0080	0.0170	0.0000 ^(a)	0.0040	0.0040	0.0000 ^(a)
La ₂ O ₃	0.0046	0.00436	0.00429	0.0045	0.00428	0.00432	0.00430
Li ₂ O	0.0376	0.0345	0.0354	0.0368	0.0392	0.0384	0.0382
MgO	0.0363	0.0355	0.0358	0.0368	0.0344	0.0347	0.0346
MnO ₂	0.0011	0.00118	0.00115	0.00120	0.00113	0.00113	0.00114
MoO ₃	0.0022	0.00220	0.00215	0.00202	0.0021	0.00210	0.0020
Na ₂ O	0.1003	0.0964	0.1110	0.0976	0.1020	0.1000	0.1050
Nd ₂ O ₃	0.0090	0.00810	0.00784	0.00804	0.00817	0.00823	0.0082
NiO	0.0042	0.00433	0.00435	0.00427	0.00442	0.00426	0.0042
P ₂ O ₅	0.0007	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)
PdO	0.0004	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)
Pr ₆ O ₁₁	0.0007	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)	0.0007 ^(a)
Rb ₂ O	0.0004	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)
Rh ₂ O ₃	0.0004	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)
RuO ₂	0.0011	0.0016	0.0012	0.0011 ^(a)	0.0011	0.0011	0.0011 ^(a)

TABLE A.3. (contd)

Oxide	Target	19-1	19-2	19-3	19-4	19-5	19-6
SO ₃	0.0020	0.0020 ^(a)	0.0020 ^(a)	0.0020 ^(a)	0.0020 ^(a)	0.0020 ^(a)	0.0020 ^(a)
SiO ₂	0.4801	0.4760	0.4670	0.4900	0.4700	0.4700	0.4710
Sm ₂ O ₃	0.0004	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)	0.0004 ^(a)
SrO	0.0007	0.00074	0.00073	0.00076	0.00074	0.00073	0.00072
TiO ₂	0.0000	0.00017	0.00015	0.00016	0.00026	0.00026	0.0000 ^(a)
Y ₂ O ₃	0.0004	0.00037	0.00037	0.00039	0.00036	0.00037	0.00036
ZrO ₂	<u>0.0429</u>	<u>0.0400</u>	<u>0.0400</u>	<u>0.0426</u>	<u>0.0399</u>	<u>0.0396</u>	<u>0.0379</u>
Sum	1.000	0.99485	1.00554	1.01565	0.98849	0.98764	0.98829

(a) Below analytical detection limit or not analyzed--target value assumed.

TABLE A.4. Summary Statistics for Six Replicate Analyses of CVS-I Glass
CVS1-19 Conducted Over Three Months

<u>Oxide</u>	<u>Target</u>	<u>Analyzed Values^(a)</u>		
		<u>Mean</u>	<u>SD</u>	<u>%RSD</u>
Al ₂ O ₃	0.0636	0.06378	0.001534	2.40
B ₂ O ₃	0.1142	0.11566	0.002422	2.09
BaO	0.0007	0.00071	0.000011	1.54
CaO	0.0275	0.02820	0.000780	2.77
CdO	0.0055	0.00547	0.000161	2.94
CeO ₂	0.0011	0.00121	0.000119	9.85 ^(b)
Cr ₂ O ₃	0.0009	0.00097	0.000041	4.16
Cs ₂ O	0.0011	0.00110	0.000110	9.96
CuO	0.0011	0.00108	0.000030	2.78
F	0.0022	0.00220	0.000000	0.00 ^(c)
Fe ₂ O ₃	0.0568	0.05498	0.000711	1.29
K ₂ O	0.0000	0.00550	0.006380	115.99 ^(d)
La ₂ O ₃	0.0046	0.00434	0.000082	1.90
Li ₂ O	0.0376	0.03708	0.001846	4.98
MgO	0.0363	0.03530	0.000916	2.60
MnO ₂	0.0011	0.00115	0.000029	2.49
MoO ₃	0.0022	0.00209	0.000076	3.62
Na ₂ O	0.1003	0.10200	0.005380	5.27
Nd ₂ O ₃	0.0090	0.00809	0.000143	1.77
NiO	0.0042	0.00430	0.000078	1.80
P ₂ O ₅	0.0007	0.00070	0.000000	0.00 ^(c)
PdO	0.0004	0.00040	0.000000	0.00 ^(c)
Pr ₆ O ₁₁	0.0007	0.00070	0.000000	0.00 ^(c)
Rb ₂ O	0.0004	0.00040	0.000000	0.00 ^(c)
Rh ₂ O ₃	0.0004	0.00040	0.000000	0.00 ^(c)
RuO ₂	0.0011	0.00120	0.000200	16.67 ^(b)

TABLE A.4. (contd)

Oxide	Target	Analyzed Values ^(a)		
		Mean	SD	%RSD
SO ₃	0.0020	0.00200	0.000000	0.00 ^(c)
SiO ₂	0.4801	0.47400	0.008367	1.76
Sm ₂ O ₃	0.0004	0.00040	0.000000	0.00 ^(c)
SrO	0.0007	0.00073	0.000014	1.86
TiO ₂	0.0000	0.00016	0.000095	57.26 ^(d)
Y ₂ O ₃	0.0004	0.00037	0.000011	2.96
ZrO ₂	0.0429	0.04000	0.001506	3.76

- (a) SD = standard deviation; %RSD = percent relative standard deviation.
- (b) One or more values set equal to the target value (since the oxide was not detected) were used for the computations.
- (c) The oxide was not detected in any of the replicate analyses, and hence all data values were set equal to the target value. This yields a mean equal to the target value and zero SD and %RSD.
- (d) Oxide was not present in the glass, but was detected in several replicates. The summary statistics are based on the positive values as well as the non-detects set equal to zero (the target value). This yields a smaller mean and larger SD and %RSD than would be obtained by omitting the non-detects.

APPENDIX B

CVS-I VISCOSITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE FULCHER EQUATION

APPENDIX B

CVS-I VISCOSITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE FULCHER EQUATION

Viscosity was measured at three to five temperatures for each of the CVS-I glasses. Table B.1 contains the viscosity at temperature data. These data were plotted for each glass, a curve was fitted graphically, and values for viscosity at 1150°C (η_{1150}) and temperature at which viscosity is 10 Pa·s (T_{10}) were determined. Linear mixture models were then fitted to a natural log transformation of η_{1150} and a reciprocal transformation of T_{10} , as discussed in Section 5.1.1.

Late in the CVS-I study it was decided to investigate fitting the viscosity at temperature data for each glass to the Fulcher equation:

$$\ln \eta = A + B / (T - T_0) , \quad (B.1)$$

where A, B, and T_0 are the Fulcher equation coefficients and T is temperature in °C. The results are summarized in Table B.2. Note that it was necessary to delete a few viscosity at temperature values because of concern that the results were affected by crystals in the glasses. The number of data points for each glass that were used to fit the Fulcher equation varied between 2 and 5. Since the Fulcher equation contains three coefficients, the equation fit the data exactly or nearly exactly in all cases. Physically meaningless values of the Fulcher equation coefficients were obtained for glass #18, which only had three data points. Table B.2 also compares the η_{1150} values predicted using the fitted Fulcher equation for each glass to the values obtained by the graphical fit (from Table 5.2). The comparison is very good, and indicates that the Fulcher equation can be used in lieu of the previous graphical technique. However, it is clear that viscosity data should be taken for at least five distinct temperatures for each glass. This recommendation will be implemented during CVS-II.

TABLE B.1. Viscosity at Temperature Data for CVS-I Glasses

Glass	Test Temp. (°C)	Viscosity Initial (Pa·s)	Viscosity Final (Pa·s)	Viscosity Change (Pa·s)	Time (min)	Rate of Change (mPa)
CVS1-1	1250	2.54	2.51	-0.03	23	-0.02
	1150	5.81	5.81	0.00	23	0.00
	1050	16.69	16.79	0.10	23	0.07
	949	72.38	72.38	0.00	20	0.00 ^(a)
CVS1-2	1248	5.81	5.96	0.15	23	0.11
	1149	13.58	13.72	0.14	23	0.10
	1050	38.32	38.32	0.00	23	0.00
	951	156.46	156.46	0.00	23	0.00
CVS1-3	1149	2.39	2.48	0.10	23	0.07
	1050	6.48	6.51	0.03	23	0.02
	951	21.78	21.84	0.06	23	0.04
	852	121.81	124.12	2.31	23	1.67 ^(b)
CVS1-4	1149	8.79	8.81	0.02	23	0.01
	1051	28.95	28.92	-0.03	23	-0.02
	951	140.45	142.76	2.31	23	1.67
CVS1-5	1348	3.19	3.10	-0.09	23	-0.07
	1250	6.02	6.05	0.03	23	0.02
	1150	13.18	13.17	-0.02	23	-0.01
	1050	35.11	35.05	-0.06	23	-0.04
	950	118.89	111.50	-7.39	23	-5.36
CVS1-6	1052	5.59	5.54	-0.05	23	-0.03
	952	22.73	22.64	-0.09	23	-0.07
	851	171.56	171.25	-0.31	23	-0.22 ^{(c), (b)}
CVS1-7	1348	6.75	6.84	0.09	23	0.07
	1248	19.47	20.08	0.62	23	0.45
	1148	75.15	74.38	-0.77	23	-0.56
CVS1-8	1350	4.57	4.27	-0.30	23	-0.22
	1252	10.21	10.24	0.03	23	0.02
	1152	36.16	61.54	25.38	23	18.39 ^{(d), (b)}
CVS1-9	1251	1.58	1.60	0.02	23	0.01
	1152	3.98	4.08	0.10	23	0.07
	1052	36.16	51.93	15.77	23	11.43 ^{(d), (b)}
CVS1-10	1449	7.98	7.88	-0.09	23	-0.07 ^(b)
	1350	13.83	13.92	0.09	23	0.07
	1250	30.80	31.11	0.31	23	0.22
	1150	83.47	82.70	-0.77	23	-0.56

TABLE B.1. (contd)

Glass	Test Temp. (°C)	Viscosity Initial (Pa·s)	Viscosity Final (Pa·s)	Viscosity Change (Pa·s)	Time (min)	Rate of Change (mPa)
CVS1-11	1251	5.68	5.66	-0.02	23	-0.02
	1152	14.48	14.43	-0.05	23	-0.03
	1052	153.94	152.09	-1.85	23	-1.34 ^(b)
	952	277.82	269.50	-8.32	23	-6.03 ^(b)
CVS1-12	1148	0.42	0.42	0.00	23	0.00
	1049	0.88	0.89	0.01	23	0.01
	952	2.31	2.25	-0.06	23	-0.04
	852	10.47	10.47	0.00	23	0.00 ^(b)
	752	131.67	130.90	-0.77	23	-0.56 ^(b)
CVS1-13	1247	1.55	1.56	0.01	23	0.01
	1148	3.36	3.37	0.01	23	0.01
	1049	9.83	9.83	0.00	18	0.00 ^(e)
	1049	9.63	9.63	0.00	5	0.00 ^(e)
	949	46.75	46.75	0.00	23	0.00
CVS1-14	1249	1.41	1.42	0.01	23	0.01
	1150	3.37	3.38	0.01	23	0.01
	1051	11.38	11.38	0.00	23	0.00
	950	61.29	62.52	1.23	23	0.89
CVS1-15	1251	1.30	1.27	-0.03	23	-0.02
	1151	2.53	2.48	-0.05	23	-0.04
	1051	5.88	5.81	-0.07	23	-0.05
	951	17.80	18.14	0.34	23	0.25
	851	79.16	80.70	1.54	23	1.12 ^(b)
CVS1-16	1348	2.89	2.91	0.02	23	0.02
	1249	6.48	6.49	0.01	23	0.01
	1149	18.02	18.02	0.00	23	0.00
	1049	113.81	128.74	14.94	23	10.82 ^{(d), (b)}
CVS1-17	1252	1.04	1.04	0.00	23	0.00
	1152	2.22	2.21	-0.01	23	-0.01
	1052	5.83	5.88	0.05	23	0.04
	953	23.10	23.25	0.15	23	0.11
CVS1-18	1251	0.77	0.61	-0.17	23	-0.12 ^(f)
	1152	.	.	.	.	.
	1052	4.62	4.62	0.00	23	0.00
	952	12.23	12.57	0.34	23	0.25 ^(g)

TABLE B.1. (contd)

Glass	Test Temp. (°C)	Viscosity Initial (Pa·s)	Viscosity Final (Pa·s)	Viscosity Change (Pa·s)	Time (min)	Rate of Change (mPa)
CVS1-19	1251	2.46	2.48	0.02	23	0.02
	1151	5.73	5.73	0.00	23	0.00
	1051	16.35	16.60	0.25	23	0.18
	951	64.53	65.76	1.23	23	0.89
CVS1-20	1252	2.52	2.50	-0.02	23	-0.01
	1152	5.51	5.54	0.02	23	0.02
	1053	15.31	15.28	-0.03	23	-0.02
	953	53.90	53.90	0.00	23	0.00
CVS1-21	1249	4.14	4.14	0.00	23	0.00
	1150	9.58	9.58	0.00	23	0.00
	1049	28.12	28.46	0.34	17	0.33 ^(h)
	950	138.75	139.06	0.31	23	0.22
CVS1-22	1351	4.43	4.39	-0.04	23	-0.03
	1252	11.20	11.17	-0.03	23	-0.02
	1153	35.97	45.77	9.79	23	7.10 ^{(d), (b)}
CVS1-23	1252	2.66	2.66	0.00	23	0.00
	1153	5.55	5.56	0.01	23	0.01
	1053	13.91	13.89	-0.02	23	-0.01
	953	44.72	44.78	0.06	23	0.04

(a) Time less due to bumped table.

(b) Denotes data not used to produce results in Table B.3. These data were omitted because of 1) high rate of change, 2) large viscosity values, and 3) extreme temperature values where little data were collected. The data points of types (2) and (3) to omit were chosen based on a series of temperature-mixture model fits as discussed in the text.

(c) Variation in readings during run.

(d) Denotes data not used (because of high Rate of Change) to produce results in Table B.2.

(e) Adjustments in electric furnace caused reading variations.

(f) Temperature data errors.

(g) Unknown noise in graph.

(h) Time less due to bumped spindle.

TABLE B.2. Results of Fitting the Fulcher Equation to the Viscosity at Temperature Data for Each CVS-I Glass

Glass	# Points Fitted ^(a)	Fulcher Equation Coefficients			Graphical η_{1150} (Pa·s)	Fulcher Predicted η_{1150} (Pa·s)
		A	B	T ₀		
CVS1-1	4 of 4	-5.31	5390.83	387.05	5.8	5.8
CVS1-2	4 of 4	-5.14	6367.00	326.47	13.6	13.3
CVS1-3	4 of 4	-6.47	6286.50	294.28	2.4	2.4
CVS1-4	3 of 3	-7.11	7998.68	287.57	8.8	8.7
CVS1-5	5 of 5	-5.72	7937.47	194.09	13.2	13.2
CVS1-6	3 of 3	-6.30	5392.86	379.94	2.0	2.0
CVS1-7	3 of 3	-6.86	8127.95	420.63	75.2	72.9
CVS1-8	2 of 3	-5.67	7000.00	375.91	36.2	29.3
CVS1-9	2 of 3	-7.18	7000.00	333.99	4.0	4.1
CVS1-10	4 of 4	-2.56	4100.51	563.65	83.5	83.8
CVS1-11	4 of 4	(b)	(b)	(b)	14.5	(b)
CVS1-12	5 of 5	-5.18	2995.90	454.08	0.4	0.4
CVS1-13	5 of 5	-4.48	3586.72	518.39	3.4	3.3
CVS1-14	4 of 4	-5.99	5055.15	449.86	3.4	3.4
CVS1-15	5 of 5	-5.47	5493.19	293.09	2.5	2.6
CVS1-16	3 of 4	-6.15	7080.86	365.44	18.0	17.8
CVS1-17	4 of 4	-5.14	4146.93	451.94	2.2	2.2
CVS1-18	3 of 3	-34.31	135565.10	-2730.03	1.5	1.9
CVS1-19	4 of 4	-6.45	7170.87	275.46	5.7	5.8
CVS1-20	4 of 4	-6.53	7629.94	228.06	5.5	5.7
CVS1-21	4 of 4	-3.90	4025.10	494.15	9.5	9.4
CVS1-22	2 of 3	-6.16	7000.00	435.70	36.0	38.1
CVS1-23	4 of 4	-6.00	7237.84	214.12	5.6	5.7

- (a) Viscosity data at certain temperature values were not used in the fitting process due to high rates of change (see Table B.1), which are indicative of crystallinity. These data points are marked with a '*' in Table B.1.
- (b) The non-linear least squares routine did not converge for this glass.

Also investigated was modeling of viscosity at temperature data from all glasses as a simultaneous function of temperature and composition. This was done by expressing the three coefficients of the Fulcher equation as linear functions of composition:

$$\ln \eta = \sum_{i=1}^{10} A_i X_i + \sum_{i=1}^{10} B_i X_i / (T - \sum_{i=1}^{10} T_i X_i) . \quad (\text{B.2})$$

Results of fitting this model to the viscosity at temperature data of Table B.1 (with data points marked ^(b) omitted) are given in Table B.3. Figure B.1 shows the predicted versus measured viscosity values. Table B.4 compares the η_{1150} values predicted by this fitted model to those from Table B.2 (determined by the graphical technique and fitting the Fulcher equation to the data for each glass) as well as η_{1150} values predicted by a linear mixture model fitted to the predicted Fulcher equation values.

It is clear from Table B.3 and Figure B.1 that the combined Fulcher-linear mixture model fits the viscosity at temperature data for the CVS-I glasses fairly well. However, the fact that the 95% confidence intervals for many of the 30 coefficients (parameters) include zero indicates that not all of the coefficients are needed, and that the model may overfit the data. It was decided not to pursue developing a reduced form of the full combined model due to the preliminary nature of the CVS-I data analyses.

The combined temperature-composition viscosity modeling approach shows sufficient promise that it will be used for CVS-II instead of the approach used for CVS-I (modeling η_{1150} and T_{10} as functions of composition). Such an approach has the flexibility of allowing prediction of viscosity for any temperature, not just 1150°C.

TABLE B.3. Fitted Viscosity Model in Which the Fulcher Equation Coefficients A, B, and T_0 are Expressed as Linear Functions of Composition

Non-Linear Least Squares Summary Statistics

Source	DF	Sum of Squares	Mean Square
Regression	30	513.36573581	17.11219119
Residual	47	0.96913073	0.02061980
Uncorrected Total	77	514.33486653	
(Corrected Total)	76	135.71382274	

Parameter	Estimate	Asymptotic Std. Error	Asymptotic 95% Confidence Interval	
			Lower	Upper
A1	-5.12897	7.697542	-20.61438	10.35645
A2	-13.87933	11.997269	-38.01466	10.25600
A3	-13.44667	11.119859	-35.81688	8.92354
A4	-7.53382	39.892023	-87.78600	72.71836
A5	-18.98154	30.049290	-79.43275	41.46967
A6	-9.56769	21.287040	-52.39157	33.25620
A7	-15.82911	16.232345	-48.48429	16.82606
A8	3.04839	24.250173	-45.73653	51.83332
A9	-16.96152	17.439987	-52.04616	18.12311
A10	-12.75484	24.997127	-63.04244	37.53276
B1	10663.06961	16312.315523	-22152.98762	43479.12684
B2	6079.71939	26113.521001	-46453.76664	58613.20542
B3	9967.10028	24637.104568	-39596.22703	59530.42760
B4	-18602.04086	92322.209303	-204329.86716	167125.78544
B5	12965.49467	67176.485102	-122175.79637	148106.78570
B6	19469.64900	42560.561058	-66150.92433	105090.22233
B7	33548.08495	37230.651480	-41350.12235	108446.29226
B8	8049.52537	53889.739770	-100362.35409	116461.40484
B9	20226.02032	34258.221982	-48692.44632	89144.48695
B10	24793.17604	53925.753145	-83691.15280	133277.50488
T1	493.32651	773.185883	-1062.11865	2048.77166
T2	268.34092	1292.985078	-2332.80251	2869.48434
T3	-718.04375	1222.172646	-3176.73133	1740.64382
T4	-786.08474	4595.485335	-10030.98376	8458.81428
T5	241.17082	3206.268565	-6208.99210	6691.33374
T6	-924.32798	1948.886545	-4844.97139	2996.31543
T7	-1504.04584	1777.062225	-5079.02424	2070.93256
T8	121.41734	2631.507589	-5172.47877	5415.31345
T9	641.09098	1513.173371	-2403.01296	3685.19492
T10	-978.01362	2612.690383	-6234.05449	4278.02725

Note: The viscosity at temperature values without #'s in Table B.1 were used to fit the model using nonlinear least squares. The above output is from the SAS (1990) nonlinear regression procedure NLIN.

Note: 40 observations hidden

FIGURE B.1. Plot of Predicted Versus Measured Viscosity at Temperature Data for the Combined Fulcher-Linear Mixture Model from Table B.3

TABLE B.4. Viscosity at 1150°C Predicted by the Combined Fulcher-Linear Mixture Model of Table B.3 Compared to Corresponding Values from Graphical Technique and Other Modeling Approaches

Glass	Graphical η_{1150} (Pa·s)	Fulcher Predicted η_{1150} (Pa·s)	Mixture Model Predicted η_{1150} (Pa·s)	Fulcher-Linear Mixture Model Predicted η_{1150} (Pa·s)
CVS1-1	5.8	5.8	7.1	6.8
CVS1-2	13.6	13.3	16.9	13.7
CVS1-3	2.4	2.4	2.8	2.8
CVS1-4	8.8	8.7	8.8	9.1
CVS1-5	13.2	13.2	10.8	12.4
CVS1-6	2.0	2.0	1.9	1.8
CVS1-7	75.2	72.9	50.	75.2
CVS1-8	36.2	29.3	38.3	28.7
CVS1-9	4.0	4.1	3.5	3.5
CVS1-10	83.5	83.8	75.0	81.3
CVS1-11	14.5	(a)	12.7	12.7
CVS1-12	0.4	0.4	0.3	0.4
CVS1-13	3.4	3.3	3.7	3.5
CVS1-14	3.4	3.4	3.6	3.3
CVS1-15	2.5	2.6	2.2	2.6
CVS1-16	18.0	17.8	12.2	12.8
CVS1-17	2.2	2.2	3.2	2.5
CVS1-18	1.5	1.9	1.9	1.6
CVS1-19	5.7	5.8	7.1	6.8
CVS1-20	5.5	5.7	7.1	6.3
CVS1-21	9.5	9.4	8.8	9.1
CVS1-22	36.0	38.1	38.3	28.7
CVS1-23	5.6	5.7	6.2	6.4

Note: The Graphical and Fulcher Predicted η_{1150} values are from the last two columns of Table B.2. The Mixture Model Predicted η_{1150} values are from a linear mixture model fitted to the Fulcher Predicted η_{1150} values. The Fulcher-Linear Mixture Predicted η_{1150} values are from the combined model in Table B.3.

(a) The non-linear least squares routine did not converge for this glass.

APPENDIX C

CVS-I ELECTRICAL CONDUCTIVITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE ARRHENIUS EQUATION

APPENDIX C

CVS-I ELECTRICAL CONDUCTIVITY AT TEMPERATURE DATA AND RESULTS FROM FITTING THE ARRHENIUS EQUATION

Electrical conductivity was measured at three to five temperatures for each of the CVS-I glasses. Table C.1 contains the electrical conductivity at temperature data. These data were plotted for each glass, a curve was fitted graphically, and values for electrical conductivity at 1150°C (ϵ_{1150}) were determined. A linear mixture model was then fitted to a square root transformation of ϵ_{1150} , as discussed in Section 5.1.2.

Late in the CVS-I study it was decided to investigate fitting the electrical conductivity at temperature data for each glass to the Arrhenius equation:

$$\ln \epsilon = A + B/T, \quad (C.1)$$

where A and B are the Arrhenius equation coefficients and T is temperature in K. The results are summarized in Table C.2. The number of data points for each glass that were used to fit the Arrhenius equation varied between 3 and 5. Since the Arrhenius equation contains two coefficients, none of the equations fit the data exactly (as was the case for viscosity). Table C.2 also compares the ϵ_{1150} values predicted using the fitted Arrhenius equation for each glass to the values obtained by the graphical fit (from Table 5.2). The comparison is very good, and indicates that the Arrhenius equation can be used in lieu of the previous graphical technique. However, in CVS-II electrical conductivity data should be taken for at least four or five distinct temperatures for each glass.

TABLE C.1. Electrical Conductivity at Temperature Data for CVS-I Glasses

<u>Glass</u>	<u>Test Temp. (°C)</u>	<u>Electrical Conductivity (S/m)</u>	<u>Glass</u>	<u>Test Temp. (°C)</u>	<u>Electrical Conductivity (S/m)</u>
CVS1-1	1239	25.1	CVS1-13	1238	46.6
	1140	18.4		1141	33.2
	1040	12.2		1041	21.8
	940	6.6		941	13.6
CVS1-2	1239	35.3	CVS1-14	1238	46.6
	1141	25.5		1142	34.7
	1041	16.8		1041	22.7
	941	9.6		942	13.9
CVS1-3	1137	33.3	CVS1-15	1239	78.0
	1040	21.1		1141	55.4
	941	12.5		1041	39.8
	841	6.2		942	24.5
CVS1-4	1239	14.3	CVS1-16	1239	35.2
	1141	8.7		1140	26.1
	1042	4.9		1040	17.1
	942	2.3		938	10.1
CVS1-5	1339	51.8	CVS1-17	1239	40.2
	1241	42.7		1142	28.3
	1141	31.6		1042	17.3
	1040	20.7		942	9.7
CVS1-6	939	12.3	CVS1-18	1239	90.1
	1238	75.4		1141	61.3
	1139	43.1		1042	42.8
	1040	24.6		942	25.6
CVS1-7	940	13.9	CVS1-19	843	12.6
	1337	16.4		1238	33.3
	1240	10.8		1142	24.5
	1140	6.7		1042	15.0
CVS1-8	1041	3.6	CVS1-20	944	8.4
	1338	19.7		1238	39.5
	1241	13.6		1142	25.3
	1141	8.4		1042	15.9
CVS1-9	1239	13.3	CVS1-21	939	9.4
	1141	8.1		1240	12.9
	1041	4.2		1140	7.6
	943	2.3		1040	4.2
CVS1-10	1438	46.6	CVS1-22	939	1.9
	1340	35.2		1338	19.7
	1241	28.2		1242	14.0
	1142	19.9		1142	8.9
CVS1-11	1239	11.7	CVS1-23	1040	5.3
	1141	7.3		1239	40.2
	1041	3.9		1142	27.0
	940	1.8		1042	16.8
CVS1-12	1138	55.6		940	10.3
	1040	35.2			
	940	19.5			
	842	8.7			
	742	2.8			

TABLE C.2. Results of Fitting the Arrhenius Equation to the Electrical Conductivity at Temperature Data for Each CVS-I Glass

Glass	# Points Fitted	Arrhenius Equation Coefficients		Graphical ϵ_{1150} (S/m)	Arrhenius Predicted ϵ_{1150} (S/m)
		A	B		
CVS1-1	4	4.07	-8184.8	18.7	18.7
CVS1-2	4	4.29	-8022.7	26.0	26.0
CVS1-3	4	5.21	-8886.9	35.6	35.6
CVS1-4	4	5.53	-11272.0	9.1	9.1
CVS1-5	5	3.82	-7107.9	33.5	30.7
CVS1-6	4	6.54	-10366.0	47.4	47.3
CVS1-7	4	4.91	-10792.0	6.9	6.9
CVS1-8	3	4.51	-9869.6	8.8	8.8
CVS1-9	4	5.26	-11014.0	8.4	8.4
CVS1-10	4	3.21	-6810.4	20.6	20.6
CVS1-11	4	5.51	-11527.0	7.5	7.5
CVS1-12	5	7.17	-10802.0	65.9	65.4
CVS1-13	4	4.29	-7627.4	34.2	34.2
CVS1-14	4	4.26	-7554.1	35.0	34.9
CVS1-15	4	4.43	-7069.4	58.2	58.2
CVS1-16	4	4.04	-7646.3	26.4	26.4
CVS1-17	4	4.97	-8852.5	28.6	28.5
CVS1-18	5	5.38	-8254.0	65.7	65.5
CVS1-19	4	4.70	-8704.5	24.3	24.3
CVS1-20	4	4.83	-8747.3	26.9	26.9
CVS1-21	4	5.65	-11624.0	8.1	8.0
CVS1-22	4	4.20	-9368.9	9.2	9.2
CVS1-23	4	4.62	-8379.0	28.1	28.0

Also investigated was modeling of electrical conductivity at temperature data from all glasses as a simultaneous function of temperature and composition. This was done by expressing the two coefficients of the Arrhenius equation as linear functions of composition:

$$\ln \epsilon = \sum_{i=1}^{10} A_i x_i + \sum_{i=1}^{10} B_i x_i / T. \quad (C.2)$$

Results of fitting the model (C.2) to the electrical conductivity at temperature (K) data of Table C.1 are given in Table C.3. Figure C.1 shows the predicted versus measured electrical conductivity values. Table C.4 compares the ϵ_{1150} values predicted by this fitted model to those from Table C.2 (determined by the graphical technique and fitting the Arrhenius equation to the data for each glass) as well as ϵ_{1150} values predicted by a linear mixture model fitted to the predicted Arrhenius equation values.

It is clear from Table C.3 and Figure C.1 that the combined Arrhenius-linear mixture model fits the electrical conductivity at temperature data for the CVS-I glasses fairly well. However, the fact that the 95% confidence intervals for many of the 20 coefficients (parameters) include zero indicates that not all of the coefficients are needed, and that the model may overfit the data. It was decided not to pursue developing a reduced form of the full combined model due to the preliminary nature of the CVS-I data analyses.

The combined temperature-composition electrical conductivity modeling approach shows sufficient promise that it will be used for CVS-II instead of the approach used for CVS-I (modeling ϵ_{1150} as a function of composition). Such an approach has the flexibility of allowing prediction of electrical conductivity for any temperature, not just 1150°C.

TABLE C.3. Fitted Electrical Conductivity Model in Which the Arrhenius Equation Coefficients A and B are Expressed as Linear Functions of Composition

Analysis of Variance					
Source	DF	Sum of Squares	Mean Square	F Value	Prob>F
Model	19	67.87720	3.57248	110.544	0.0001
Error	74	2.39148	0.03232		
C Total	93	70.26868			
Root MSE		0.17977	R-square	0.9660	
Dep Mean		-1.80173	Adj R-sq	0.9572	
C.V.		-9.97765			
Parameter Estimates					
Variable	DF	Parameter Estimate	Standard Error	T for H0: Parameter=0	Prob > T
SiO ₂	1	4.747226	1.73737330	2.732	0.0079
B ₂ O ₃	1	9.571850	3.01985411	3.170	0.0022
Na ₂ O	1	-1.523348	5.55934833	-0.274	0.7848
Li ₂ O	1	-2.855309	7.52719282	-0.379	0.7055
CaO	1	9.079969	5.53847920	1.639	0.1054
MgO	1	4.311880	6.04655012	0.713	0.4780
Fe ₂ O ₃	1	6.665853	4.02801400	1.655	0.1022
Al ₂ O ₃	1	1.199155	4.20108482	0.285	0.7761
ZrO ₂	1	4.717894	4.94871700	0.953	0.3435
OTHERS	1	18.343511	5.38432320	3.407	0.0011
SiO ₂ /T	1	-12717	2389.0903506	-5.323	0.0001
B ₂ O ₃ /T	1	-16649	4048.7937514	-4.112	0.0001
Na ₂ O/T	1	14117	7580.6603483	1.862	0.0665
Li ₂ O/T	1	36151	10269.510127	3.520	0.0007
CaO/T	1	-20057	7566.3750736	-2.651	0.0098
MgO/T	1	-14664	8248.5214788	-1.778	0.0795
Fe ₂ O ₃ /T	1	-12440	5509.3799002	-2.258	0.0269
Al ₂ O ₃ /T	1	-6847.458425	5623.1193760	-1.218	0.2272
ZrO ₂ /T	1	-12222	6799.0975449	-1.798	0.0763
OTHERS/T	1	-26457	7404.5923087	-3.573	0.0006

TABLE C.4. Electrical Conductivity at 1150°C (1423°K) Predicted by the Combined Arrhenius-Linear Mixture Model of Table C.3 Compared to Corresponding Values from Graphical Technique and Other Modeling Approaches

Glass	Graphical ϵ_{1150} (S/m)	Arrhenius Predicted ϵ_{1150} (S/m)	Mixture Model Predicted ϵ_{1150} (S/m)	Arrhenius-Linear Mixture Model Predicted ϵ_{1150} (S/m)
CVS1-1	18.7	18.7	24.2	23.6
CVS1-2	26.0	26.0	24.0	22.3
CVS1-3	35.6	35.6	30.2	28.5
CVS1-4	9.1	9.1	8.6	8.6
CVS1-5	33.5	30.7	43.4	39.4
CVS1-6	47.4	47.3	46.6	44.9
CVS1-7	6.9	6.9	7.9	7.9
CVS1-8	8.8	8.8	8.0	8.0
CVS1-9	8.4	8.4	10.1	10.1
CVS1-10	20.6	20.6	13.3	12.9
CVS1-11	7.5	7.5	10.2	10.0
CVS1-12	65.9	65.4	49.9	47.1
CVS1-13	34.2	34.2	34.4	33.9
CVS1-14	35.0	34.9	35.7	35.7
CVS1-15	58.2	58.2	66.9	67.1
CVS1-16	26.4	26.4	27.2	27.2
CVS1-17	28.6	28.5	24.8	25.2
CVS1-18	65.7	65.5	62.6	64.1
CVS1-19	24.3	24.3	24.2	23.6
CVS1-20	26.9	26.9	24.2	23.6
CVS1-21	8.1	8.0	8.6	8.6
CVS1-22	9.2	9.2	8.0	8.0
CVS1-23	28.1	28.0	29.3	28.0

Note: The Graphical and Arrhenius Predicted ϵ_{1150} values are from the last two columns of Table C.2. The Mixture Model Predicted ϵ_{1150} values are from a linear mixture model fitted to the Arrhenius Predicted ϵ_{1150} values. The Arrhenius-Linear Mixture Predicted ϵ_{1150} values are from the combined model in Table C.3.

APPENDIX D

NORMALIZED ELEMENTAL RELEASES AND STANDARD DEVIATIONS
FROM DUPLICATE MCC-1 AND PCT LEACH TESTS

APPENDIX D

NORMALIZED ELEMENTAL RELEASES AND STANDARD DEVIATIONS FROM DUPLICATE MCC-1 AND PCT LEACH TESTS

Normalized elemental releases and leachate pH values from duplicate 28-day MCC-1 and 7-day PCT leach tests of CVS-I glasses are given in Tables D.1 and D.2, respectively. Standard deviations (SD) and percent relative standard deviations (%RSD) for normalized B release (before and after natural log transformations) from the MCC-1 and PCT leach tests are given in Tables D.3 and D.4, respectively.

TABLE D.1. Normalized Elemental Release and pH Data from Duplicate 28-day MCC-1 Tests (90°C, DIW, 10m⁻¹) Performed on CVS-I Glasses

Glass Sample	Normalized ^(a) Elemental Release Rates (g/m ²)						pH
	Si	B	Li	Mo	Na	Cs	
CVS1-1A	8.812	12.332	11.782	12.139	12.147	10.653	9.92
CVS1-1B	9.168	12.614	12.125	12.345	12.577	8.716	9.98
CVS1-2A	6.915	7.588	7.189	8.934	7.385	8.279	10.17
CVS1-2B	6.721	7.331	7.189	7.538	7.439	8.673	9.91
CVS1-3A	10.175	14.904	14.992	14.797	14.987	9.855	9.41
CVS1-3B	11.498	16.238	16.129	16.193	16.253	10.644	9.74
CVS1-4A	65.602	191.318	162.581	178.682	181.192	102.497	9.65
CVS1-4B	64.103	188.103	161.290	175.890	179.695	102.497	9.65
CVS1-5A	10.121	11.190	10.353	11.168	10.628	13.798	10.01
CVS1-5B	10.721	11.768	10.568	12.005	11.032	14.192	10.12
CVS1-6A	45.940	119.614	105.991	116.701	90.566	9.855	10.06
CVS1-6B	44.823	122.990	111.214	120.052	95.418	9.855	9.76
CVS1-7A	7.422	10.804	10.280	11.726	10.569	9.461	9.81
CVS1-7B	7.572	11.190	10.731	10.888	10.933	11.038	9.89
CVS1-8A	11.594	17.942	16.710	18.706	17.229	15.374	9.71
CVS1-8B	11.873	17.814	16.753	17.868	17.390	15.769	9.72
CVS1-9A	45.788	158.641	148.817	123.402	150.302	67.805	9.24
CVS1-9B	45.788	158.805	148.817	124.798	150.302	70.959	9.24
CVS1-10A	2.512	2.566	3.183	2.234	2.599	2.168	8.65
CVS1-10B	2.883	2.917	3.484	2.513	3.011	2.602	8.37
CVS1-11A	6.716	8.220	8.172	7.775	8.309	5.919	9.15
CVS1-11B	6.817	8.282	8.172	7.880	8.327	5.919	9.18
CVS1-12A	49.349	118.483	122.581	120.052	122.685	114.323	10.86
CVS1-12B	49.349	118.483	122.581	117.260	122.685	98.554	10.87
CVS1-13A	179.562	672.026	632.258	647.721	617.398	98.554	10.55
CVS1-13B	195.682	709.003	673.118	684.016	657.207	106.439	10.63
CVS1-14A	24.013	75.241	69.677	47.183	58.917	9.855	10.04
CVS1-14B	23.860	72.026	66.452	44.670	56.456	10.250	10.14
CVS1-15A	73.022	213.505	174.501	199.900	174.724	57.950	12.37
CVS1-15B	73.787	207.074	169.585	198.504	170.272	56.767	12.37
CVS1-16A	10.074	15.498	14.043	18.147	14.463	14.980	10.42
CVS1-16B	12.691	18.199	16.710	17.868	17.557	17.740	10.54
CVS1-17A	20.075	38.842	40.645	37.691	40.570	34.691	10.94
CVS1-17B	20.404	39.357	41.075	38.528	41.126	39.422	10.98
CVS1-18A	5.933	24.437	24.332	20.611	23.977	14.899	10.59
CVS1-18B	5.882	23.666	22.980	20.518	22.500	11.393	11.47
CVS1-19A	8.723	12.727	12.926	11.980	12.765	9.684	9.84
CVS1-19B	9.168	13.318	13.441	12.596	13.343	10.653	9.92
CVS1-20A	8.679	12.276	12.183	11.775	12.187	9.297	9.88
CVS1-20B	8.990	12.727	12.812	12.049	12.792	9.103	9.88
CVS1-21A	60.729	204.180	178.280	192.641	190.177	102.497	9.66
CVS1-21B	61.478	207.395	177.204	195.433	194.669	102.497	9.64
CVS1-22A	11.156	17.042	16.753	17.589	16.746	15.769	9.80
CVS1-22B	12.072	17.685	17.441	17.310	17.229	15.769	9.73
CVS1-23A	----- Results Discarded as Obviously Erroneous -----						
CVS1-23B	12.025	15.371	15.713	14.637	15.629	14.006	9.96

(a) Releases normalized using target compositions from Tables 4.6 and A.1.

TABLE D.2. Normalized Elemental Release and pH Data from Duplicate 7-day PCTs (90°C, DIW, 2000m⁻¹) Performed on CVS-I Glasses

Glass Sample	Normalized ^(a) Elemental Release Rates (g/m ²)						pH
	Si	B	Li	Mo	Na	Cs	
CVS1-1C	0.167	0.521	0.515	0.439	0.403	0.058	10.92
CVS1-1D	0.167	0.521	0.543	0.439	0.403	0.053	10.92
CVS1-2C	0.054	0.066	0.154	0.061	0.064	0.057	11.43
CVS1-2D	----- No Sample Analyzed -----						11.41
CVS1-3C	0.176	0.900	0.814	0.487	0.593	0.051	9.85
CVS1-3D	0.168	0.828	0.768	0.449	0.566	0.034	9.85
CVS1-4C	0.482	20.289	16.667	22.335	16.697	1.498	9.67
CVS1-4D	0.598	20.989	17.204	23.731	17.370	1.971	9.67
CVS1-5C	0.321	0.357	0.464	0.325	0.192	0.130	11.22
CVS1-5D	0.315	0.354	0.461	0.328	0.190	0.166	11.22
CVS1-6C	0.313	6.053	4.854	4.188	3.032	0.126	10.07
CVS1-6D	0.311	6.174	4.931	4.188	3.059	0.122	10.07
CVS1-7C	0.114	0.287	0.330	0.306	0.340	0.136	10.91
CVS1-7D	0.114	0.287	0.331	0.302	0.338	0.150	10.91
CVS1-8C	0.265	1.254	0.745	1.161	0.805	0.075	10.42
CVS1-8D	0.265	1.222	0.743	1.159	0.805	0.073	10.43
CVS1-9C	0.346	10.816	8.495	7.259	7.803	0.915	8.69
CVS1-9D	0.343	11.169	8.710	7.538	7.991	0.930	8.69
CVS1-10C	0.103	0.125	0.382	0.094	0.095	0.030	9.78
CVS1-10D	0.105	0.128	0.390	0.095	0.095	0.028	9.74
CVS1-11C	0.043	0.104	0.188	0.065	0.109	0.054	10.00
CVS1-11D	0.038	0.093	0.186	0.067	0.090	0.059	9.98
CVS1-12C	0.842	4.794	4.301	4.928	4.541	1.577	11.12
CVS1-12D	0.809	4.530	4.040	4.551	4.248	1.636	11.13
CVS1-13C	0.759	14.132	12.903	13.262	12.449	1.183	10.37
CVS1-13D	0.813	14.011	12.903	12.982	12.377	1.025	10.37
CVS1-14C	0.153	9.968	8.172	1.256	5.863	0.473	9.63
CVS1-14D	0.145	9.727	7.849	1.368	5.718	0.150	9.64
CVS1-15C	0.990	18.971	11.275	19.404	14.134	2.957	13.04
CVS1-15D	0.944	18.585	11.121	18.845	13.855	2.641	13.02
CVS1-16C	0.247	0.524	0.265	0.470	0.540	0.150	12.02
CVS1-16D	0.235	0.521	0.267	0.466	0.540	0.154	11.99
CVS1-17C	0.630	2.241	2.075	2.234	2.177	0.986	11.57
CVS1-17D	0.696	2.228	2.075	2.234	2.431	0.895	11.58
CVS1-18C	1.516	11.125	7.957	10.631	7.954	1.429	12.25
CVS1-18D	1.547	11.350	8.172	10.833	8.125	1.709	12.25
CVS1-19C	0.165	0.517	0.529	0.439	0.430	0.063	10.29
CVS1-19D	0.167	0.529	0.538	0.456	0.437	0.068	10.29
CVS1-20C	0.156	0.453	0.466	0.391	0.394	0.053	10.17
CVS1-20D	0.156	0.458	0.469	0.401	0.397	0.048	10.15
CVS1-21C	0.467	19.051	15.806	19.543	15.723	1.735	9.68
CVS1-21D	0.452	18.650	15.376	19.543	15.349	1.754	9.68
CVS1-22C	0.259	1.122	0.704	1.125	0.762	0.065	9.81
CVS1-22D	0.259	1.116	0.703	1.120	0.758	0.069	9.81
CVS1-23C	0.230	0.521	0.530	0.483	0.484	0.060	10.28
CVS1-23D	0.228	0.528	0.539	0.490	0.489	0.065	10.30

(a) Releases normalized using target compositions from Tables 4.6 and A.1.

TABLE D.3. Standard Deviations (SD) and Percent Relative Standard Deviations (%RSD) Before and After Natural Logarithmic Transformations of Normalized^(a) Boron Release Data From Duplicate 28-Day MCC-1 Leach Tests

<u>Glass</u>	<u>Mean (g/m²)</u>	<u>Untransformed SD (g/m²)</u>	<u>RSD (%)</u>	<u>Log Transformed SD (g/m²)</u>	<u>RSD (%)</u>
CVS1-1	12.47	0.1994	1.60	0.0160	0.63
CVS1-2	7.46	0.1817	2.44	0.0244	1.21
CVS1-3	15.57	0.9433	6.06	0.0606	2.21
CVS1-4	189.71	2.2733	1.20	0.0120	0.23
CVS1-5	11.48	0.4087	3.56	0.0356	1.46
CVS1-6	121.30	2.3872	1.97	0.0197	0.41
CVS1-7	11.00	0.2729	2.48	0.0248	1.04
CVS1-8	17.88	0.0905	0.51	0.0051	0.18
CVS1-9	158.72	0.1160	0.07	0.0007	0.01
CVS1-10	2.74	0.2482	9.05	0.0907	9.01
CVS1-11	8.25	0.0438	0.53	0.0053	0.25
CVS1-12	118.48	0.0000	0.00	0.0000	0.00
CVS1-13	690.52	26.1467	3.79	0.0379	0.58
CVS1-14	73.63	2.2733	3.09	0.0309	0.72
CVS1-15	210.29	4.5474	2.16	0.0216	0.40
CVS1-16	16.85	1.9099	11.34	0.1136	4.03
CVS1-17	39.10	0.3642	0.93	0.0093	0.25
CVS1-18	24.05	0.5452	2.27	0.0227	0.71
CVS1-19	13.02	0.4179	3.21	0.0321	1.25
CVS1-20	12.50	0.2189	2.55	0.0255	1.01
CVS1-21	205.79	2.2738	1.10	0.0110	0.21
CVS1-22	17.36	0.4547	2.62	0.0262	0.92
CVS1-23	15.37 ^(b)	--	--	--	--
<hr/>					
Pooled Values					
All Data		5.77	3.93	0.0393	2.26
w/o #13		1.51	(c)	(c)	(c)
w/o #16		(c)	3.17	0.0317	(c)

(a) Normalized with respect to target compositions.

(b) Only one of the two duplicate samples was analyzed.

(c) Not computed, since not of interest.

TABLE D.4. Standard Deviations (SD) and Percent Relative Standard Deviations (%RSD) Before and After Natural Logarithmic Transformations of Normalized^(a) Boron Release Data From Duplicate 7-Day PCT Leach Tests

<u>Glass</u>	<u>Mean (g/m²)</u>	<u>Untransformed SD (g/m²)</u>	<u>RSD (%)</u>	<u>Log Transformed SD (g/m²)</u>	<u>RSD (%)</u>
CVS1-1	0.521	0.0000	0.00	0.0000	0.00
CVS1-2	0.066 ^(b)	--	--	--	--
CVS1-3	0.864	0.0509	5.89	0.0590	-40.09
CVS1-4	20.639	0.4950	2.40	0.0240	0.79
CVS1-5	0.356	0.0021	0.60	0.0060	-0.58
CVS1-6	6.113	0.0856	1.40	0.0140	0.77
CVS1-7	0.287	0.0000	0.00	0.0000	0.00
CVS1-8	1.238	0.0226	1.83	0.0183	8.56
CVS1-9	10.992	0.2496	2.27	0.0227	0.95
CVS1-10	0.126	0.0021	1.68	0.0168	-0.81
CVS1-11	0.098	0.0078	7.90	0.0790	-3.41
CVS1-12	4.662	0.1867	4.00	0.0400	2.60
CVS1-13	14.072	0.0856	0.61	0.0061	0.23
CVS1-14	9.848	0.1704	1.73	0.0173	0.76
CVS1-15	18.778	0.2729	1.45	0.0145	0.50
CVS1-16	0.522	0.0021	0.41	0.0041	-0.62
CVS1-17	2.234	0.0092	0.41	0.0041	0.51
CVS1-18	11.238	0.1591	1.42	0.0142	0.58
CVS1-19	0.523	0.0085	1.62	0.0162	-2.50
CVS1-20	0.456	0.0035	0.78	0.0078	-0.99
CVS1-21	18.850	0.2836	1.50	0.0150	0.51
CVS1-22	1.119	0.0042	0.38	0.0038	3.37
CVS1-23	0.524	0.0049	0.94	0.0094	-1.46
<hr/> Pooled Values-All		0.1609	2.59	0.0259	--

(a) Normalized with respect to target compositions.

(b) Only one of the two duplicate samples was analyzed.

APPENDIX E

HWVP MEASUREMENT AND TEST EQUIPMENT (M&TE) LIST

APPENDIX E

HWVP MEASUREMENT AND TEST EQUIPMENT (M&TE) LIST

The Measurement and Test Equipment (M&TE) list applicable during CVS-I follows.

M&TE CONTROL LISTING

Item #	M&TE Control #	M&TE Description	Location	Calibration Interval	Custodian	Calib. Agency	CTG LVL	Remarks
1	364-06-01-001	Balance, Electronic	325/22	3 months	MJ Schweiger	HEDL	1	Mettler HL32
2	364-06-01-006	Balance, Electronic	325/22	3 months	MJ Schweiger	HEDL	1	Mettler PC4400
3	364-06-01-019	Balance, Electronic	PSL/417	3 months	MJ Schweiger	HEDL	1	Mettler PM4600
4	364-06-01-020	Balance, Electronic	PSL/421	3 months	MJ Schweiger	HEDL	1	Mettler PM4600
5	364-06-01-021	Balance, Electronic	PSL/421	3 months	MJ Schweiger	HEDL	1	Sartorius A-200S
6	371-06-03-002	Balance, Electronic	325/500	3 months	DA Cochran	HEDL	1	Mettler PN323
7	364-86-02-007	Calibrated Weights	PSL/417	Yearly	MJ Schweiger	HEDL	1	
8	364-45-10-008	pH Meter/Ionalyzer	PSL/421	Yearly	MJ Schweiger	HEDL	1	Orion 601A
9	364-45-10-003	pH Meter, Digital	325/22	Yearly	MJ Schweiger	HEDL	1	Orion 601A
10	364-47-01-005	Micrometer, Digital	PSL/417	Yearly	MJ Schweiger	HEDL	1	Micro 200
11	[WA62900]	Digital Viscometer-1	PSL/417	3 months	MJ Schweiger	USER	2	Brookfield, used with Spindle 2
12	[WA72484]	Digital Viscometer-2	325/23	3 months	MJ Schweiger	USER	2	Brookfield used with Springle 3
13	[WA16373]	Impedance Bridge	PSL/417	3 months		USER	2	Used with probe 1
14	[WA54922]	Data Acquisition/Control Unit	PSL/421		MJ Schweiger	HEDL	1	HP3297A
15	TC-4-237797	Thermister	PSL/421	2 Years	MJ Schweiger	HEDL	1	
16	TC-5-237797	Thermister	PSL/421	2 Years	MJ Schweiger	HEDL	1	
17	TC-7-237797	Thermister	PSL/421	2 Years	MJ Schweiger	HEDL	1	
18	TC-8-237797	Thermister	PSL/421	2 Years	MJ Schweiger	HEDL	1	
19	TC-9-237797	Thermister	PSL/421	2 Years	MJ Schweiger	HEDL	1	
20	364-79-06-003	T/C Readout K, J, T	PSL/417	6 Months	MJ Schweiger	HEDL	1	Fluke
21	364-79-06-012	T/C Readout Thermister	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 5800
22	364-79-06-014	T/C Readout Type S	PSL/417	Yearly	MJ Schweiger	HEDL	1	Fluke 2168A
23	364-79-06-015	T/C Readout Type K	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 650
24	364-79-06-016	T/C Readout Type S	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 660
25	364-79-06-017	T/C Readout Type S	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 660
26	364-79-06-018	T/C Readout Type S	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 660 Furnace #1
27	364-79-06-019	T/C Readout Type S	PSL/417	Yearly	MJ Schweiger	HEDL	1	Omega 650
28	[FA00250]	T/C Readout Type S	325/500	6 months	DA Cochran	PNL	1	Fluke
29	364-79-01-005	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	
30	364-79-01-006	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	

Item #	M&TE Control #	M&TE Description	Location	Calibration Interval	Custodian	Calib. Agency	CTG LVL	Remarks
31	364-79-01-007	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	
32	364-79-01-009	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	
33	388-79-01-009	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	
34	388-79-01-011	Thermometer	PSL/417	Yearly	MJ Schweiger	HEDL	1	
35	301845-6700	Thermocouple Type k	PSL/417	2 Years	MJ Schweiger	HEDL	1	5-15-87*
36	301845-6701	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	5-15-87*
37	301845-6702	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	*
38	301845-6703	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	*
39	301845-6704	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	*
40	301845-6705	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	*
41	TC-5-203359	Thermocouple Type K	PSL/417	2 years	MJ Schweiger	HEDL	1	*
42	306307-06	Thermocouple Type S	PSL/417	2 years	MJ Schweiger	HEDL	1	10-16-87* (#1)
43	306307-07	Thermocouple Type S	PSL/417	2 years	MJ Schweiger	HEDL	1	*
44	306307-08	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	12-17-87* (#3)
45	306307-09	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	*
46	306307-10	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	
47	306307-11	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	
48	306307-12	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	9-20-87* (#4)
49	306307-13	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	*
50	306307-14	Thermocouple Type S	PSL/417	2 Years	MJ Schweiger	HEDL	1	*
51	306307-15	Thermocouple Type S	PSL/417	2 years	MJ Schweiger	HEDL	1	*
52	306307-16	Thermocouple Type S	PSL/417	2 years	MJ Schweiger	HEDL	1	*
53	306307-17	Thermocouple Type S	PSL/417	2 years	MJ Schweiger	HEDL	1	*
54	306307-18	Thermocouple Type S	325/500	2 years	WM Gerry	HEDL	1	7-24-87*
55	306307-19	Thermocouple Type S	325/500	2 years	WM Gerry	HEDL	1	7-24-87*
56	[WB62837]	LCR Meter	PSL/417	3 months	MJ Schweiger	USER	2	HP4282A

*Thermocouples that are in use need to be calibrated every 2 years. When thermocouples are placed in service, a date will be added to the item number on the M&TE list along with a number in parentheses to indicate the furnace number it is being used with. Thermocouples not placed in service need to be recalibrated every 5 years.

Prepared by MJ Schweiger, 1-24-90 Project Manager/Task Leader S. O. Bates 1-24-90
MJ Schweiger Date SO Bates Date

Project (Task Number) HWP- QA Plan WTC-006 Rev.2
1VJ00102
1VJ00303

DISTRIBUTION

<u>No. of Copies</u>		<u>No. of Copies</u>	
12	DOE/Office of Scientific and Technical Information L. P. Juffy, EM-1 Assistant Secretary DOE Office of Environmental Restoration & Waste Management Forrestal Building Washington, DC 20585 J. W. Bartlett, RW-1 DOE Office of Civilian Radioactive Waste Management Forrestal Building Washington, DC 20585		H. Brandt DOE Savannah River Operations Office P.O. Box A Aiken, SC 29801 W. S. Ketola DOE West Valley Project P.O. Box 191 West Valley, NY 14171 R. S. Poulter Fluor Daniels, Inc. 333 Michelson Irvine, CA 92730
14	DOE Office of Environmental Restoration and Waste Management GTN Washington, DC 20545 Attn: K. A. Chacey, EM-361 J. A. Coleman, EM-35 C. R. Cooley, EM-55 S. Cowan, EM-30 J. J. Fiore, EM-423 C. Frank, EM-50 M. Frei, EM-34 T. S. Gutmann J. E. Lytle, EM-30 T. W. McIntosh, EM-343 H. F. Walter, EM-343 J. Hennessey, EM-343 F. D. Pettit, NI-04 J. C. Tseng, EM-36 J. K. Bates Argonne National Laboratory Chemical Technology Division 9700 S. Cass Avenue Argonne, IL 60439-4837	6	West Valley Nuclear Services Co. P.O. Box 191 West Valley, NY 14171 Attn: S. M. Barnes R. R. Borisch R. A. Palmer J. L. Mahoney V. Jain D. E. Carl
		10	Westinghouse Savannah River Co. Savannah River Site Aiken, SC 29801 Attn: J. T. Carter D. F. Bickford J. A. Gentilucci N. D. Hudson C. M. Jantzen J. R. Knight, 773A S. L. Marra M. J. Plodinec C. T. Randall, 7042 L. O. Westphal

No. of
Copies

ONSITE

10 DOE Richland Field Office

J. H. Anttonen
K. W. Bracken
R. W. Brown
S. T. Burnum
L. Erickson
R. A. Gilbert
P. E. LaMont
R. L. Long
E. C. Norman
G. H. Sanders

32 Westinghouse Hanford Company

C. A. Augustine
J. N. Appel
J. R. Baker
D. G. Braide
R. B. Calmus
R. P. Colburn
J. R. Erben
P. Felise
R. L. Gibby
H. D. Harmon
J. O. Honeyman
L. L. Humphries
W. C. Miller
R. B. Morson
F. D. Nankani
D. J. Newland
M. J. Rackley
E. D. Randklev
K. R. Shah
P. S. Schaus
R. G. Seymour
M. A. Siano
R. A. Smith
G. E. Stegen
L. D. Swenson
D. V. Vo
R. A. Watrous
E. T. Weber III

No. of
Copies

J. Weber
C. N. Wilson
G. Woodcock
D. D. Wodrich

55 Pacific Northwest Laboratory

C. R. Allen
R. M. Bean
W. F. Bonner
L. A. Bray
H. C. Burkholder
C. C. Chapman
J. M. Creer
D. E. Eakin
R. E. Einziger
M. L. Elliott
J. R. Gaskill
G. A. Jensen
P. R. Hrma (7)
L. K. Holton
W. L. Kuhn
D. E. Larson (2)
J. L. McElroy
B. P. McGrail
G. B. Mellinger
E. V. Morrey
J. M. Perez, Jr.
G. F. Piepel (7)
B. A. Pulsipher
P. E. Redgate
R. J. Robertus
W. A. Ross
P. A. Scott
J. M. Seay
G. J. Sevigny
P. Sliva
M. R. Smith
P. A. Smith
H. D. Smith
D. M. Strachan
J. H. Westsick, Jr.
K. D. Wiemers
Publishing Coordination
Technical Report Files (5)

END

DATE
FILMED

7 / 1 / 93