41/3-9-9295 ②
PREPARED FOR THE U.S. DEPARTMENT OF ENERGY,
UNDER CONTRACT DE-AC02-76-CHO-3073

PPPL-2823
UC-424

PPPL-2823

PLASMA-MATERIALS INTERACTION ISSUES FOR THE INTERNATIONAL
THERMONUCLEAR EXPERIMENTAL REACTOR (ITER)

BY

S.A. COHEN, R.F. MATTAS, K.A. WERLEY

February 1992

PPPL

PRINCETON
PLASMA PHYSICS
LABORATORY

PRINCETON UNIVERSITY, PRINCETON, NEW JERSEY

NOTICE

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial produce, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

NOTICE

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the:

Office of Scientific and Technical Information
P.O. Box 62
Oak Ridge, TN 37831;
Prices available from (615) 576-8401.

Available to the public from the:

National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, Virginia 22161
703-487-4650

**Plasma-Materials Interaction Issues for the
International Thermonuclear Experimental Reactor (ITER)***

S.A. Cohen

Plasma Physics Laboratory, Princeton University, Princeton, NJ 08544

R. F. Mattas

Argonne National Laboratory, Argonne, IL 60439

K.A. Werley

Los Alamos National Laboratory, Los Alamos, NM 87545

Abstract

Analysis of proposed operating scenarios for the International Thermonuclear Experimental Reactor has yielded predictions for the power and particle fluxes onto the material surfaces facing the plasma. The particles, mostly deuterium, tritium, and helium ions, would have energies in the range of 50-2000 eV and fluxes up to $5 \times 10^{23} / \text{m}^2 \text{ s}$. Lower fluxes of multi-MeV electrons and alpha particles may also strike the plasma-facing surfaces, primarily during transient events. The peak power fluxes onto the plasma-facing surfaces during normal operation are expected to be 5-100 MW/m², but much higher during transient events. At the extreme conditions expected for steady-state operation, commonly used heat-removal structures are unable to withstand either the high sputter erosion rates or power loads. To reduce the time-averaged power flux, active control of the plasma position is specified to sweep the plasma heat load across larger areas of plasma-facing components. However, the cyclic heat load creates fatigue lifetime problems. Solutions to these lifetime and reliability problems by 1) changes in machine design and operation, 2) redeposition mechanisms, and 3) changes in materials, will be discussed. A proposed accelerated-life test facility for prototype divertor plate development is described.

* Prepared for the U.S. Department of Energy under contract DE-AC02-76-CHO-3073

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
1

I. Introduction

In 1987, four parties, the EC, Japan, USA, and USSR, agreed to perform a joint conceptual design study for the next large magnetic confinement fusion device.¹ The design of this device, called the International Thermonuclear Experimental Reactor (ITER), was completed in November 1990.² It is a quasi-steady-state, D/T-burning, 1 GW fusion power, magnetic plasma confinement facility with a tokamak configuration.³ (See figure 1.) The exhaust of fusion power and helium ash formed by D/T fusion events, the maintenance of plasma purity, and the achievement of long plasma-facing-component (PFC) lifetimes, collectively termed power and particle control (PPC) issues, were among the most challenging aspects of the ITER conceptual design.⁴ Furthermore, these must be achieved in a manner consistent with safety⁵ and reliability requirements and transferable to a DEMO reactor. This paper summarizes many of the conclusions reached in the conceptual design study, presents new simplified physical pictures of some of the important plasma-materials interaction phenomena, discusses methods to reduce the severity of potential problems, and notes a novel way to test plasma-facing components prior to the construction of ITER.

II. Power and particle control: general aspects

Operation of the ITER device will require the exhaust of power deposited in the plasma by the energetic fusion alphas generated in fusion reactions and the subsequent removal of the thermalized helium ash. The component chosen to meet these requirements is a high-recycling divertor.⁶ Its advantage for helium ash removal is clear in that it concentrates the helium atoms in a relatively small volume appropriate for exhaust by conventional vacuum pumps. Its appropriateness for power exhaust is open to question because divertors, of virtually any design, only subtend a small fraction of the available surface area of the vacuum vessel and hence are likely to have higher peak power loads than ideally possible. However, several other requirements for the power and particle control system also favor high-recycling divertors. These are low impurity generation and long component lifetime. High-recycling divertors promote long PFC lifetimes by reducing impurity generation and promoting redeposition through the formation of cold, dense plasmas ($T_e < 30$ eV) near material surfaces and also by their ability to screen impurities. (Impurity screening is predicted to occur due to the sheath electric field and plasma flow towards the divertor, both entrapping the sputtered impurities after ionization and redirecting them back onto the divertor plate.)

The purpose of the extensive calculations reported below^{3,7,8} was to check the adequacy of high-recycling divertors for achieving the low divertor plasma temperature and favorable flow conditions just described. These calculations were performed for a wide range of proposed ITER operating conditions and for a variety of "conventional" divertor designs and materials. From engineering considerations⁸ of detailed divertor designs, including heat removal capability, sublimation temperatures, and safety margin, it was found that the peak power load tolerable was about 30 MW/m², if the heat profile on the divertor plate could be

swept, and somewhat less than half that value without sweeping. As described in section III, several, but not all, operating scenarios would produce sufficiently low divertor power loads and erosion rates. It is not coincidental that those scenarios with adequately low peak power loads and erosion rates also have adequate helium exhaust.

The divertor must also withstand off-normal operation, the prime example of which is the disruption.³ Predictions of disruption erosion, described in section VI, show that disruptions are the major divertor lifetime limiting factor and hence merit extensive R&D efforts.⁹

The so-called "first wall" in ITER is exposed to lesser fluxes of power and particles than the divertor. Radiation (mainly synchrotron, Bremsstrahlung, and x-ray) would give a nearly uniform loading of 0.1 MW/m^2 . Plasma bombardment is expected to be negligible, causing about 1 cm erosion after 3×10^7 seconds of full power plasma operation (≈ 1 burn-year). (The erosion is about 5 times higher for pure C and 20 times lower for W wall armor.)¹⁰ About 1% of the alphas born in the plasma are expected to be promptly lost. These 4.5 MeV helium ions would impact the walls in highly localized fashion,¹¹ causing power loads up to 0.5 MW/m^2 on submillimeters or sections of the wall between toroidal field coils. Special cooling and design for these segments would be required.

III. Divertor plasma parameters

Three divertor plasma parameters, the electron temperature at the divertor sheath, the ion flux through the sheath, and the power load onto the divertor plate, set the requirements for the engineering design and materials suitable for the divertor plate, and are used to predict the divertor's ability to exhaust helium and fusion power and to shield impurities. These three plasma parameters are largely determined by the power flow into the scrape-off layer (SOL), the plasma density at the separatrix (n_s), the plasma recycling at the divertor plate, the plasma cross-field thermal conductivity in the SOL ($\chi_{\perp}$), the divertor plate and magnetic field geometry, and the radiation energy losses in the SOL. The divertor plate lifetime with respect to sputter erosion is particularly sensitive to the peak sheath electron temperature, $\hat{T}_e$. Radiation-enhanced sublimation (RES) for carbon is sensitive to both $\hat{T}_e$ and the material temperature. For carbon, a peak material temperature below $\sim 1700 \text{ C}^\circ$ is estimated as a requirement to avoid runaway RES erosion.³ (Lower material temperatures are required at higher electron temperatures.)

To calculate the expected divertor plate temperature, the exact power load profile, divertor plate design (materials and dimensions) and power load sweeping scenario (amplitude and frequency) must be used. As described in section V, sweeping⁴ is necessary to reduce the divertor plate temperature, even for scenarios A1 and B1, see table 1.

For ITER, the divertor plasma parameters are predicted by use of 2-d numerical fluid plasma codes.¹² The above-named sources, transport properties, and boundary conditions, which are used as inputs to the codes, come from a small database collected from tokamaks. Extrapolations of these data to ITER results in an

uncertainty due to experimental measurements, incomplete understanding of the physical processes, and the paucity of data.

Additionally, the 2-d fluid codes are "ideal" in the sense that they do not include toroidal and poloidal (up/down) asymmetries known to exist, a realistic impurity radiation model, and power variation due to lack of perfect burn-rate control. Estimated corrections are applied after the "ideal" 2-d predictions are made. The net correction, termed a "physics safety factor," consists of both the omitted physics and the uncertainties.^{3,7}

Separate physics safety factors are calculated for $\hat{T}_e$ and peak power load $\hat{P}$ for both the inner and outer divertor plates and for each different operating scenario. Though $\hat{T}_e$ is more sensitive than $\hat{P}$ to small changes in n_s or $\chi_\perp$, both are bounded by the constraint of energy conservation. If $\chi_\perp$ is different than assumed, the power load profile width, typically 0.1 m on the divertor plate, changes inversely as $\hat{P}$. An additional safety (or peaking) factor of ~ 1.5 for $\hat{P}$ derives from engineering concerns such as gaps between divertor tiles, or misalignments due to thermal expansion during operation or inaccuracies during installation.

It is anticipated that improvements in the $\chi_\perp$, n_s database will be achieved within the next few years as a result of physics R&D. These may - or may not - result in lower predicted values for $\hat{T}_e$ and $\hat{P}$. They will, at least, give a more definite statement of the heat removal requirements. Improvements in plasma control, such as the ability to rotate or avoid locked modes, would reduce the power load $\sim 50\%$. Recent, but preliminary,¹³ assessments of SOL impurity radiation also predict substantially lower $\hat{T}_e$ and $\hat{P}$. This latter effect also warns of the proximity of a density limit¹⁴ to the selected operating space.

In Table I are listed $\hat{T}_e$, $\hat{P}$, and $\hat{\Gamma}$ (the peak ion flux) for the outer divertor plate, calculated for three operating scenarios, ignited, long-pulse, and steady-state. A safety factor of 3 is recommended for $\hat{T}_e$. If $\hat{T}_e$ is higher, $\hat{\Gamma}$ is lower. The physics safety factor for $\hat{P}$ has been applied in the fourth line and both physics and engineering safety factors in the fifth line. The values for these parameters are averages of those predicted by five similar 2-d fluid codes.³ Parameters predicted at the inner divertor plate are generally comparable to those at the outer, when safety factors have been included.

From the perspective of impurity generation due to physical sputtering, a sheath electron temperature below ~ 75 eV is considered necessary, particularly for W.^{15,16,17} Scenarios A1 and B1 satisfy this criterion, even after the application of a safety factor to $\hat{T}_e$. Scenario B6, steady-state, non-inductive operation, does not have an acceptable $\hat{T}_e$ value. This is mainly due to the low assumed separatrix density and a high applied auxiliary power, both associated with current drive requirements.

Table I: Peak divertor plasma sheath parameters^{7,15}

	A1 (ignited)	B1 (long pulse)	B6 (steady state)
$\hat{\Gamma}$ (ideal) $10^{23}/m^2s$	4.3	2.7	1.7
$\hat{T}_e$ (ideal) eV	15	15	130
$\hat{P}$ (ideal) eV	6	4.2	22
$\hat{P}$ (with physics safety factor) MW/m ²	20	14	75
$\hat{P}$ (with all safety factors) MW/m ²	30	21	105

IV. Erosion/redeposition

The expected lifetime of the divertor plates has been estimated based upon sputtering erosion. (See Section VI for a discussion of the potentially more severe disruption erosion.) For graphite, it is estimated that the divertor plates would need to be replaced less than 3 times during the physics phase. For tungsten tiles, less than one replacement would be needed during the technology phase for hybrid long-pulse (> 2500 sec) operation. However, steady-state operation would result in runaway erosion of either W or C, due to high T_e .

For erosion (as a divertor plate lifetime issue) dominated by physical sputtering, the ion energy and species are critically important for predicting the gross material loss rate. The plasma parameters listed in Table I set the ion energy. But, because of the exceedingly high plasma density and temperature (compared, for example, to those in sputter deposition systems used in plasma processing), the sputtered atoms may be ionized close to the point on the divertor plate from which they originated and deposited back onto the material surface. In this manner, the lifetime of the divertor plate may be lengthened relative to that predicted by the gross erosion rate alone. Using linked kinetic and Monte Carlo codes, this ratio of lifetimes, net to gross, has been predicted¹⁷ to be about 30 for ITER, depending on the plasma scenario, divertor materials, and the geometry. Here we describe a simpler way to understand the erosion/redeposition phenomenon. We also derive a scaling law for the ratio of net to gross lifetimes, including the effects of redeposition.

This discussion is based on the flux equation which describes how sputtered C ions and atoms step along the divertor plate in the (predominantly major) radial direction. In the redeposition process, sputtered C ions step along the divertor plate in the toroidal direction and C atoms step predominantly in the radial direction. The toroidal motion is not treated here in any detail because the toroidal direction is (largely) an ignorable coordinate in tokamaks. Later work must include the toroidal motion because of ripple in the toroidal field and the same features which led to an engineering safety factor on the heat load.

Consider a carbon divertor plate bombarded by a magnetized deuterium plasma. Deuterons impact the divertor plate, possibly ejecting C atoms. (In figure 2 only the ion guiding center motion is shown, though naturally the ions spiral around the field lines.) The sputtered carbon atoms proceed on straight line

trajectories until they are ionized by electron impact. Most of these carbon ions are promptly forced back towards the plate (along the magnetic field) by the combined effects of deuterium ion drag and the sheath and presheath electric fields. (Those few which penetrate to the core of the tokamak eventually are also redeposited on the divertor plates.) Because of the tilt of the plate with respect to the magnetic field and the fact that the gyro radius is shorter than the ionization mean free path, the C^+ ions impact the divertor plate a distance from where they originate. Figure 2 shows that these sputtered atoms "walk" in both the x (predominantly major radial) and z (toroidal) directions. The characteristic step sizes are set by the ionization mean-free-path, λ , and the inclination angle of the plate with respect to the flux surface, θ , and with respect to the total magnetic field, ψ . To a lesser extent, the ion gyroradius contributes. The step size in the toroidal direction is longer because of the very small angle of the total field $\psi \sim 2^\circ$, compared to $\theta \sim 15^\circ$ for the flux surfaces. Again, for a toroidally symmetric tokamak, the toroidal motion is unimportant and we subsequently ignore it, concentrating instead on the x direction, a mix of poloidal and major radial coordinates.

To estimate w' , the characteristic x -direction step size, we need to take into account both the tilt of the plate relative to the angle of incidence of B (actually the flux surface) and the distribution of ejection angles from the surface. These two effects are imbedded in w''' (convective) and w'' (diffusive) respectively (figure 3). First we compare the relative importance of these. The equation for carbon transport in the x direction,

$$\Gamma_x = -D\nabla n_C + n_C v_x, \quad (1)$$

where n_C is the carbon density above the plate, is the basis for this comparison. The carbon atom density is only appreciable within a distance λ from the divertor plate surface. As we now show, for plates even slightly tilted with respect to the flux surface, i.e., $\theta \leq 89^\circ$, the net motion along x is dominated by the plate tilt, not by the random angle of sputter emission. Start with the approximations

$$D \sim \lambda^2/2\tau, \quad (2)$$

$$\nabla n_C \sim n_C/w, \text{ and} \quad (3)$$

$$v_x \sim \lambda/\tau \tan \theta. \quad (4)$$

where τ is the time between successive sputterings of the same carbon atom. The origin of equation 2 is clear. The gradient, equation (3), arises from the x variation of sputtering which depends on the x variation of n_e and T_e . In arriving at equation (4), we have approximated the sputtered particles x -velocity by assuming that they are emitted normal to the surface only. The angle (measured from the surface, not the surface-normal to the plate) at which the diffusive and convective terms are equal,

$$D\nabla n_C = n_C v_x,$$

is readily found from (2) - (4)

$$\begin{aligned} \tan \theta &= 2w/\lambda \\ &\sim 20 \text{ cm}/10^{-2} \text{ cm} \text{ for ITER,} \end{aligned}$$

corresponding to $\theta \cong 89^\circ$.

This angle shows that only a small tilt makes the convective part of equation 1 more important than diffusion for transporting the sputtered carbon atoms away from their original locations. We thus conclude that the step size is adequately approximated by

$$w' = \lambda / \tan \theta \quad (5)$$

Note that the carbon density above the surface is determined by the deuterium sputtering,

$$n_c v_c = \Gamma_D Y \quad (6)$$

where $Y = 1.5 \times 10^{-2} (1 - E_{th}/T_e)^{\Xi}$ (7)

is an approximation¹⁸ for the sputtering yield of D on C in the electron temperature range $2 \text{ eV} < T_e < 200 \text{ eV}$, $E_{th} \cong$ threshold energy $\cong 30 \text{ eV}$ for carbon, $\Xi \sim 19$ and

$$\begin{aligned} \Gamma_D &= \text{flux of deuterium onto the surface} \\ &\sim 5 \times 10^5 n_e T_e^{1/2} \sin \psi \text{ (cm}^{-2}\text{s}^{-1}\text{)} \end{aligned} \quad (8)$$

Again, ψ is the angle between the total magnetic field and the surface (see figure 1).

The ionization mean-free-path for carbon atoms is given by

$$\lambda = v_c / n_e \langle \sigma v \rangle \quad (9)$$

where

v_c = velocity of sputtered carbon $\sim 2 \times 10^5 T_e^{1/2} \text{ (cm/s)}$,

T_e = electron temperature (eV),

n_e = electron density (cm^{-3}),

$\langle \sigma v \rangle$ = carbon ionization rate¹⁹ $= 1.5 \times 10^{-8} T_e^{1/2} \exp(-I/T_e) \text{ (cm}^3\text{/s)}$, and

$I = 11.2 \text{ eV}$ for neutral carbon.

The functional dependence for v_c on T_e is qualitative; it assumes momentum transfer at sputtering proportional to momentum gain in the sheath.

n_e and T_e do vary along x , but we assume throughout this discussion of the characteristic ionization length that they are uniform. The effect of spatially varying n_e and T_e is included later through our *ansatz* of a characteristic width w of the erosion process. This is essentially the width of the intense plasma footprint on the divertor plate.

In ITER, the ion temperature near the divertor plate is expected^{7,15} to be in the range 8-24 eV for scenario A1 to 30-100 eV for scenario B6. With safety factors, the electron temperature ranges from 15 - 45 eV for A1 to 100 - 300 eV for scenario B6. The sheath potential is about $\phi_s = 4 T_e$, and the average energy of impacting D ions is about $\phi_s + 2T_i$, though ion energies up to $\sim \phi_s + 5T_i$ must be considered because of the Maxwellian ion distribution. Hence the relevant range of deuterium ion energies is from 75 to 300 eV for scenario A1 and from 460 to 1700 eV for B6.

Impacting carbon ions can have energies as much as 10 times higher, depending on their charge states and flow velocities.

We now compare the gross erosion rate with the net loss. The gross erosion rate per cm^2 is clearly

$$R_G = \Gamma_D Y. \quad (10)$$

The net erosion is calculated based on the following picture. A 1 cm wide segment of the plate is shown in cross section in Figure 4. In one erosion time, τ , sputtered particles within w' of surface B exit the segment; those within w' to the left of A enter. For a unit area, the net change in a time τ is then

$$\begin{aligned} \text{net change} &= (\Gamma_D Y|_A - \Gamma_D Y|_B) \tau w' \\ &= (\Gamma_D Y/w) \tau w', \end{aligned} \quad (11)$$

where the difference in sputtering rates at A and B has a characteristic gradient of scale length w . In 1 sec the net loss rate is

$$R_N = \Gamma_D Y w' / w. \quad (12)$$

The gross lifetime is

$$\tau_G = T / \Gamma_D Y, \quad (13)$$

for a plate of thickness T .

The ratio of the plate's net lifetime to gross lifetime is

$$\tau_N / \tau_G = R_G / R_N = w / w'. \quad (14)$$

Using equations 5 and 9 for w' and λ we get the scaling for the net-to-gross lifetimes

$$\begin{aligned} \tau_N / \tau_G &= w n_e \langle \sigma v \rangle \tan \theta / v_c \\ &= 0.85 \times 10^{-13} n_e w e^{-I/T_e} \tan \theta. \end{aligned} \quad (15)$$

The gross lifetime alone is obtained from equations 7, 8, and 13

$$\tau_G \propto [n_e T_e^{1/2} \sin \psi (1 - E_{th}/T_e)^{19}]^{-1} \text{ seconds}. \quad (16)$$

The ratio τ_N / τ_G is shown in Fig. 5 versus $n_e w \tan \theta$, along with contours of constant τ_G . In passing we note that the limit of validity of the model is approximately $w'/w < 0.3$, which depends on T_e , w , and θ .

From examining equations 15 and 16 and figure 5 we can make the following observations:

1. The width of the plasma profile on the divertor plate, w , is proportional to $1/\sin \theta$, thus τ_N / τ_G is, to second order, independent of θ .
2. In contrast, τ_G is proportional $1/\sin \theta$ because of the decrease in flux with increasing plate tilt. Sweeping the plasma footprint across the plate has the same effect as increased tilt. Both give a longer plate life
3. Although a lower electron temperature means that ionization is more distant from the plate and that redeposition is less effective, the dramatic drop in sputter yield at lower T_e makes the net lifetime longer.

V. Engineering design of the ITER divertor

a. Divertor design

The Conceptual Design Activity (CDA) led to separate divertor designs for the physics and engineering phases.¹⁸ The major difference between the designs is

the choice of the plasma-facing material. Carbon fiber composite was selected for the physics phase based upon the large amount of experience with graphite in existing tokamaks, its capability to serve as a protective armor, and the advantage of using a low-Z material for reduced impurity effects in the plasma. Tungsten was selected for the technology phase based upon predictions for extremely low rates of sputtering erosion and reduced neutron irradiation effects. The latter also contributes to longer lifetimes. Be is considered a strong backup candidate, particularly because of the reduction in impurities and runaways observed with its use in JET. For C tiles, redeposition of eroded material is predicted to reduce the net erosion rate by a factor of about 30 over the gross erosion rate, markedly extending the divertor plate lifetime; W tiles would benefit an even greater amount.

In both the physics and technology phases, active cooling of the divertor plate, using low-temperature, low-pressure water, was selected because of long-pulse operation and safety issues⁵ at high material temperatures. Since the candidate plasma-facing materials are not considered to be structural, they must be bonded to back plates that contain the water coolant. Both copper and refractory metal alloys (e.g. Nb and Mo) are candidates for the water-cooled back plates. The designs for the physics and technology phases are illustrated in Figure 6.

The divertor designs represent a compromise between performance capability (e.g. allowable heat flux), risk/reliability, and lifetime. The basic approach used in the CDA was to design a divertor plate with the maximum lifetime (based on erosion losses) that meets the other requirements of heat removal, material temperature, and safety. To accommodate high heat fluxes and avoid high material surface temperature ($>1200^{\circ}\text{C}$) which promote RES in carbon and chemical reactivity in tungsten, the plasma-facing material thickness was reduced to about 7 mm for C and 2 mm for W. Even at this thinness, sputter erosion was predicted to require only few divertor replacements. The safety margin for coolant channel burnout is reduced at high heat fluxes, adding to the risk of component failure.

Using conventional designs and presently available materials, sweeping the heat deposition profile^{20,21} was found to be necessary to tolerate 30 MW/m^2 , based on a coolant tube burnout criteria and a limit on the allowed plate surface temperature. The required parameters of the sweeping procedure were an amplitude of $\pm 12\text{ cm}$ across the divertor plate at a frequency above 0.3 Hz. This prescription lowers the effective power load to below 6 MW/m^2 and the peak surface temperature to 1100°C . These sweeping parameters are marginally within the capability of the CDA PF system. Improvements in the safety margins would be obtained with better thermal conductivity materials, sweeping methods, and control of the plasma to produce lower power fluxes. All are difficult to obtain.

b. Thermal fatigue

However, fatigue failure of the divertor plates may occur due to cyclic thermal-load applied stresses. Thermal stress induces strain in the divertor plates, both by differential expansion from thermal gradients and by differing expansion coefficients of the various materials bonded to each other. The question is whether

a higher frequency sweeping scenario, with more strain reversals, will have a longer life due to the decrease in temperature excursions (strain range), or a shorter lifetime due to the increased number of cycles.

Below the elastic limit, the induced strain range, $\Delta\epsilon$, in the (composite) structure of the ITER divertor plates is approximately proportional to the surface temperature excursions, ΔT . (The water-cooled back plate keeps the tile back surface at nearly a fixed temperature.) The surface temperature has been calculated for several different frequencies of sweep.^{21,22} As shown in Table II, a factor of ~3.5 reduction in surface temperature excursions, which corresponds to a factor of ~3.5 reduction in strain range, can be achieved by an increase in sweep frequency, ν , from 0.2 to 2.0 Hz. The scaling is

$$\Delta\epsilon \propto 1/\nu^{0.5}, \quad (17)$$

typical for a diffusion process. (These calculations were done assuming the heat load profile expected on the reference divertor plate in the ignited ITER scenario.)

Table II: Surface temperature versus sweep frequency^{21,22}

Frequency (Hz)	Surface temperature (°C)		ΔT (°C)
	Minimum	Maximum	
0.2	400	1100	700
2.0	600	800	200

Heat-load sweeping across the ITER divertor at 0.2 Hz, the CDA design, will result in 6×10^6 cycles (1.2×10^7 stress reversals) during the technology phase; a 2.0 Hz sweep frequency will produce 10 times more strain reversals.

Fatigue lifetime can be predicted from strain-lifetime equations.²³ The stress-strain parameter (the strain range, $\Delta\epsilon$)²⁴ versus stress reversals to failure, N_f , is given in figure 7 for A723 high strength steel. The behavior of this steel is expected to be better than that of the "exotic" ITER tile materials bonded to substrates. See, for example, the single data point²⁵ calculated for the DEMO W/5%Re divertor plate assembly which has a peak power load of only 13 MW/m².

As seen in figure 7, the cycles-to-failure (CTF) increase dramatically at lower strain range,

$$CTF \sim 1/\Delta\epsilon^{3.5}. \quad (18)$$

The fatigue lifetime of the material is proportional to the CTF divided by the sweep frequency,

$$Lifetime \sim CTF/\nu. \quad (19)$$

Combining equations (17) - (19) shows that a higher sweep frequency increases the plate lifetime with respect to fatigue,

$$Lifetime \sim \nu^{0.75}. \quad (20)$$

Recent poloidal field coil design by the Japanese ITER team²² has shown how to achieve a higher sweep frequency by placing coils inside the ITER vacuum vessel. Such a configuration, though difficult because of the radiation environment as well as installation requirements, would yield a major improvement in the

predicted operation, both by lowering the surface temperature (important to RES) and increasing the lifetime.

However, the problems are not completely solved. Data from mechanically induced stresses on small samples generally show fewer cycles to failure than predicted in the "low cycle" range, 10^5 - 10^6 cycles. Furthermore, effects of hydrogen plasma on material embrittlement must be considered a synergistic effect. It should be noted that the greatest heat loads, hence stresses, are at edges such as the gaps between tiles. A fatigue-life test facility (which incorporates exposure to hydrogen plasmas) must be developed to check the accuracy of these fatigue life predictions.

VI. Disruptions and vertical displacement events³

The lifetime of plasma-facing components may be seriously reduced by the effects of disruptions and/or vertical displacement events. To evaluate the PFC lifetime, the frequency and character of these two processes must be understood and extrapolations to ITER made.

a. Categories of disruptions

Disruptions are placed into 4 categories according to cause: high β , density limit, low-q, and transient/unknown. The occurrence of disruptions of the first three types is generally predictable to $\pm 30\%$ in the appropriate plasma parameter. The last category, which includes disruptions during plasma current ramp-up/down, beam turn-on/off, and abnormal impurity influx (e.g., flakes or blooms), is highly irreproducible.

b. Disruption frequency

In many large tokamaks nearly 50% of all discharges disrupt. But operation away from high- β , low-q, and density limits has allowed two high-power heated tokamaks, TFTR and JT-60, to reduce the disruption frequency to $\sim 2\%$. Improvements in plasma control are expected to lower the attainable disruption frequency to 1% during ITER's high repeatability technology phase. The experimental physics phase of ITER is expected to experience a 5 - 10% disruption frequency at full parameters because of its need to explore a wide area of operating space. A major question is whether disruption frequency is per unit operating time or per discharge. This impacts a major benefit claimed for steady-state operation.

c. Thermal quench

Disruptions have two phases in which appreciable amounts of energy are transferred from the plasma's stored kinetic and magnetic energy reservoirs. In the first phase, the thermal quench, about 50% of the plasma's kinetic energy is lost by conduction to the plasma-facing components, mainly the divertor plate. The duration of this heat pulse has been measured to be 0.1 to 3 ms and the power deposition profile is ~ 3 times broader than in L-mode discharges. Assuming toroidal

symmetry and the measured heat load profile, both questionable extensions to ITER, the predicted peak energy load on the divertor is 12 MJ/m^2 . This intense plasma-material interaction is predicted to cause extensive material ablation.

d. Current quench

Loss of plasma position control follows loss of plasma kinetic energy. Motion is first radially inward; subsequent up/down motion is likely in highly elongated plasmas. As a result of loss of both position and the kinetic energy, the plasma current drops rapidly. This, the current quench phase, will result in a conversion of poloidal magnetic field energy to plasma heating, runaway electron generation, and electrical currents through the PFC's. Plasma energy will be radiated by impurities present in the plasma from wall contact, leading to an estimated peak energy loads on the walls of 3 MJ/m^2 in times ranging from 20 to 200 ms.

Vertical displacement events²⁶ are phenomena in which loss of plasma control precedes loss of kinetic energy. They, nonetheless, share many features with disruptions. Perhaps the major difference is the higher level of currents which flow through the PFC due to the larger and more rapid plasma motion. These larger currents, to 4 Ma in ITER, will result in larger impulsive forces on the PFC's.

e. Runaway electrons

Disruption-induced runaway electrons are predicted to have energies as high as 300 MeV, limited by synchrotron radiation losses.²⁷ The average energy will be about 40 MeV. The runaway current may well approach 10 MA. Though many tokamaks, e.g., PLT, Tore Supra, and JET, have experienced energetic runaways (to 100 MeV) at currents to $I_p/2$ ($\sim 3 \text{ MA}$ in JET), several tokamaks (DIII-D and JT-60) have observed none, raising the hopes that control of the Dreicer parameter, primarily through the plasma density, may allow elimination of runaway electron generation in ITER. As noted previously, use of Be in JET has all but eliminated runaway production.

f. Engineering considerations

Each full parameter thermal quench is predicted to erode 0.14-0.22 mm of graphite or 0.04-0.4 mm of tungsten on the divertor plates. Little dependence on the duration of the thermal quench is expected over the range of 0.1-3.0 ms. These estimates include recent experimental observations (in e-beam facilities) of enhanced graphite erosion compared to ablation models which include vapor shielding of the heat flux. No credit is taken for redeposition of eroded material due to ionization in nearby plasma. Preliminary ablation measurements in a USSR plasma gun experiments actually show ~ 30 reduction in ablation, claimed due to the vapor shielding mechanism, supporting model recent model calculations. Excluding these beneficial preliminary results, disruption erosion is about 10 times more severe than sputter erosion. The predicted erosion rates (without the benefits of plasma shielding) lead to an estimate of 9-17 replacements for carbon divertor plates in the physics phase and 4-14 replacements for tungsten divertor plates in the

technology phase. Maintenance requirements for tungsten or beryllium could be relieved by *in situ* spray techniques for re-coating the divertor plates.

Runaway electron impact has received less detailed study. The general conclusion is that carbon tile divertor plates will afford no protection to the water cooling channels from runaway electron impacts at the level predicted by the physics group. Tungsten divertor tile would afford some protection, but quantitative predictions are lacking. Sacrificial limiters are one potential method to reduce the likelihood for impacts on the coolant channels.

Torques and forces induced in the PFC by the disruptions and VDE's will require special considerations given to the wall component structural design.

VI. Helium exhaust

A helium concentration below 10% in the core plasma would relax energy confinement (plasma current) requirements and allow longer burn times in ignited, inductively driven, plasmas. Benefits in the non-inductively driven technology phase would be somewhat less.

To achieve a low core helium concentration, helium transport through three regions must be adequate. These regions are the core, the SOL, and the pump duct. The transport processes are serial, hence boundary conditions must be matched at the interfaces, namely at the separatrix and at the pump duct opening.

Measurements of core helium transport have been carried out on several machines, notably JT-60,²⁸ TEXTOR,²⁹ and TFTR.³⁰ The data have been analyzed to yield two ratios: χ/D , the ratio of plasma thermal diffusivity to helium particle diffusivity; and $C_V = n_i v_i / (D_i \nabla n_e)$, the ratio of helium convection to diffusion. (The latter ratio has an alternate definition if convection is proportional solely to D_i rather than to $D_i \nabla n_e$.)

BALDUR (1-d core plasma) simulations of ITER performance^{31,32} show ignition can be sustained for $\chi/D < 8$ and $C_V < 2$. Both these constraints can be somewhat relaxed if the ratio of the reflux of helium from the divertor region across the separatrix to the outflux is smaller than 0.9. No measurements on this interface condition have been made. However, 2-d, numerical, multifluid, SOL plasma simulations predict more than adequately small ratios, < 0.1 , of the helium reflux to the outflux.³³

Experiments performed on TFTR³⁰ show (radially resolved) $\chi/D < 4$ for three types of plasmas, L-modes, rotating L-modes, and supershots. In the supershots C_V is ~ 2 inside $r/a = 0.4$ and C_V is < 0.5 for $r/a > 0.4$. The JT-60 and TEXTOR NBI L-mode experiments show $0.65 < C_V < 1.5$. All these results are favorable for ITER attaining core helium concentrations below 10%. But there are no data yet for ELMy H-mode, diverted plasmas, which are the only plasmas appropriate for scaling to ITER.

Similarly, there are no experimental data on helium flows in the SOL. The same 2-d multifluid codes as noted above predict an outward shift of about 30 cm for the peak of the He^{++} impact profile on the divertor plate.³³ Having helium

closer to the pump duct opening would naturally aid helium exhaust. The causes of this outward shift include plate tilt, atomic physics (higher He^0 ionization potential compared to D^0) and entrapment of He^{++} in the reversed D^+/ T^+ flow away from the divertor region.

The effects of pump duct and divertor plate geometry on helium exhaust have been calculated with Monte Carlo neutral codes. These use plasma parameters from the 2-d multifluid simulations. The required pumping speed for three ITER operation scenarios are shown in Table III for different assumptions on the divertor geometry and on the flux profile on the divertor plate.³⁴ The cases marked "reference" include no shift to the helium flux profile and the "1990 - as drawn" divertor plate/pump duct geometry. The cases marked "improved" take credit for both geometry changes and the predicted outward shift of the helium flux profile. It should be noted that changes in the separatrix plasma density from those values assumed are predicted to alter the required pumping $\propto n^{-2}_s$. Measurements on JT-60 of helium exhaust show an even stronger dependence of the helium density in the pump duct versus the line-averaged density, $n_{\text{He}} \propto n^{-3}_e$.

Table III: Pumping speed at the torus required for helium exhaust

	A1	B1	B6
Reference geometry (m^3/s)	700	800	1970
Improved geometry (m^3/s)	310	340	1060

The pumping speed available at the pump duct openings is $700 \text{ m}^3/\text{s}$. Thus scenarios A1 and B1 are likely to have more than adequate helium exhaust capability. B6, however, is lacking. The reason is the low helium density at the divertor plate which arose from the low separatrix electron density required for current drive operation.

VII. Improvements in divertor operation

Improvements in the operation of ITER components which interact directly with the plasma could arise from changes in ITER design, plasma operation scenarios, or understanding of the important plasma-materials interactions issues. In the first and second categories, a major effort has been expended in the US, spurred on by perceived benefits of higher aspect ratio for the tokamak.³⁵ Operation of ITER at high aspect ratio permits a smaller plasma volume, reduced fusion and heating power, and a lower plasma current than the CDA design. These impact divertor operation in several favorable ways.³⁶

1. Lower plasma current and volume give lower stored magnetic and kinetic energy, resulting in less severe damage during each disruption.
2. The increase in volt-second capacity, compared to the CDA design, gives longer pulse lengths in both ignited and driven modes of operation. At fixed disruption probability per pulse, the ITER CDA assumption, less total

disruption damage would occur in the HARD design for each phase of operation.

3. Lower plasma current requires less auxiliary current drive power at fixed density or allows a higher plasma density for the same current drive power. For the latter option, higher density, the peak electron temperature at the divertor sheath is lower, which reduces divertor plate erosion.
4. Higher plasma density increases the plasma radiation losses attainable with seeded impurities. At fixed impurity concentration, the impurity-radiated power is proportional to $n^2 Z^3$, with about 2/3 of the power loss (for $Z < 40$) from the edge plasma ($r/a > 0.8$). Hence, by use of impurity seeding, the divertor power load is reduced more rapidly than the core energy confinement and fuel dilution are degraded.

The net effects of preliminary studies³⁶ are encouraging, though the reductions in divertor temperature and heat load are mostly of order 5 to 25 percent.

A second method discussed within the ITER group and elsewhere was to operate ITER in a single-null (SN) configuration rather than a double-null (DN). The penalty paid in divertor heat load was estimated to be only 10%, mostly due to the initial ITER assumption that 80% of the fusion power was exhausted to the outer divertors.³ What must be appreciated is that, in the SN configuration, we have an example of the new math,

$$2 \text{ meters} \supset 1.5 \text{ meters} + 1.5 \text{ meters} \quad (21)$$

where the symbol " $\supset$ " means "is better than". What equation 21 tells us is that a single 2 meter deep (the distance from the x point to the strike point) divertor will have better operating properties than two 1.5 meter deep divertors. It may also take up less space (see figure 8). Better operation results from the non-linear aspects of the energy loss channels, specifically radiation and charge exchange. Additional space savings can result if internal coils can be used to curve the flux surfaces. Their implementation is difficult due to neutron effects on insulators and conductors alike.

The third category of improvements includes changes in the divertor concept. The three most often proposed are the liquid metal divertor, the radiative divertor, and the gaseous neutralizer. Major benefits of the liquid metal concept are higher heat load capability and replenishable surfaces. Potential problems are corrosion and tritium inventory. The latter two concepts, when taken to their logical extremes, avoid plasma erosion because, at some divertor depth, the plasma will be sufficiently cooled that recombination will be complete and no plasma contacts the material surfaces. A reentrant divertor shape (see figure 8) will also increase radiation and charge exchange losses by redirecting the neutrals scattered off the divertor plate back into the hottest part of the divertor region plasma. Helium, because of its high ionization potential will more readily pass into the private flux region where pumping ducts can be located.

Investigation of the validity of these concepts is urgently needed. Some experiments must be performed in tokamaks. Other aspects could well be tested more efficiently in other devices.

The ITER Divertor Experiment and Laboratory (IDEAL)³⁷ is proposed as a means to test ITER divertor concepts, models, and prototypes in an accurate and cost-effective fashion (see figure 9). This R&D project focuses on technology issues of the reference divertor design, such as heat flux capacity, thermal fatigue in a hydrogen environment, erosion and redeposition, safety, and reliability. The IDEAL device is intended to test divertor material response to steady-state operation, to loss-of-coolant or loss-of-flow accident scenarios. Disruptions, and radiation effects are not within the scope of this proposal. Physics issues, such as parallel energy or particle transport would also be addressed. The importance of this facility for testing novel divertor concepts, such as liquid metals, gaseous targets and radiatively cooled, must also be recognized.

Design of the device has been guided by the logic that divertor testing requires full-life exposure (3×10^7 s) to hydrogen plasmas, with close replication of the parameters expected in the ITER divertor during both the physics and technology phases of operation. These parameters include plasma electron and ion temperatures, plasma density and power flow, plasma gradients, and magnetic field strength and orientation.

A linear device was chosen as the basis for IDEAL based on mirror experiment successes in ion heating to > 500 eV and electron heating to > 50 eV. However, mirror devices have not operated at densities $> 10^{14} \text{ cm}^{-3}$, a requirement for ITER divertor plasma simulations. On the cost-benefit side, we note that toroidal devices require typically 30 divertor modules while a linear machine needs only two. Single-component devices, e.g., electron or ion beams, are not suitable for integrated testing because they lack the intense hydrogen plasma environment necessary for embrittlement effects and erosion/redeposition phenomena. Earlier proposals for divertor tests in a linear plasma device have been made, e.g., ref 38.

The length and diameter of the IDEAL device were chosen by physics and engineering constraints. An excellent method for volumetric ion heating, ICRF slow waves absorbed on a magnetic beach require about 4 m of length because of the power-handling capability of RF antenna and the need for phased-array launching to assure efficient energy absorption. Though considerations of direct ohmic electron heating (as an addition) are in progress, emissive cathodes are considered undesirable because of the power loads on them (hence short lifetime) and their possibility to contaminate the plasma. Electron emission is also likely to produce collisionless electrons at high power (bias), thus reducing its ability to heat the plasma. Four more meters of length are required for tilted divertor plates of sufficient length to exceed (by a factor of 30) the toroidal step size of sputtered atoms (and the size of the pump duct opening). Three meters of length are required for adequate uniformity of the end magnetic field. Fluid code simulations showed that this total length was sufficient for collisional transfer of a quarter of the input energy from the ions to the electrons, a necessity in light of the predicted values for the ITER divertor sheath electron temperature. These simulations included radial heat transport at rates up to twice those predicted by Bohm transport. The minimum diameter of the plasma was chosen to be ~ 8 cm in the heating section to match $k_{\perp}$ of the ICRF. This value, in conjunction with the available ICRF power, also satisfies the requirement that the power flow in the plasma parallel to B was $> 150 \text{ MW/m}^2$,

the value predicted for ITER during ignited operation, (see Table I).

Superconducting magnets were selected for their low operational cost and "off-the-shelf" availability (from the medical NMR imaging industry). The magnetic field strength requirement, 5T, naturally arises from ITER's value. This serendipitously matches the frequency range of existing ICRF (H-fundamental) power supplies at PPPL. With this configuration, the IDEAL device would produce plasma equivalent to a flux tube of $\sim 50 \text{ cm}^2$ cross section, originating at the ITER divertor plate and extending about 0.5 meters away in the poloidal direction. It is in this region in ITER that most processes important to heat load, erosion/redeposition, and helium exhaust occur.

The plasma shape and position would be controlled by quadrupole coils, which also will aid plasma stability if the natural cusp-like configuration and ICRF ponderomotive force are insufficient. Neglecting these stabilizing effects, for the IDEAL magnetic beach configuration, $\int dl/B$ shows that interchange modes will be stabilized if on-axis field ripple is less than $\sim 5\%$, a value easily achievable with proper coil design. Kink mode stability limits the ohmic heating current to less than $\sim 10 \text{ kA}$. This is, however sufficient to provide 3 MW of heating power at $T_e \sim 100 \text{ eV}$. Kelvin-Helmholtz instabilities are considered unimportant because the stagnated flow in a high-recycling divertor causes $v_A \gg c_s \gg v_{\text{flow}}$.

Plasma parameters were predicted for IDEAL with the same B2 code used to model the ITER divertor plasma. At high gas feed and recycling ($R=0.97$), a divertor sheath plasma with high density ($\sim 10^{15} \text{ cm}^{-3}$), low temperature ($T_e \sim T_i \sim 8 \text{ eV}$), and high parallel power flow ($\sim 200 \text{ MW/m}^2$) is predicted, essentially equivalent to that shown in Table I for ignited operation. Higher temperature, lower density plasmas, comparable to some technology phase scenarios, are predicted at lower gas sources and lower recycling. In the heating region, the predicted ion and electron temperatures are 200-500 eV and 40-90 eV, respectively, in the high and low density modes of operation. These then give the gradients necessary to properly simulate impurity flows. Furthermore, the divertor plate would be oriented at $\sim 5^\circ$ with respect to the magnetic field, appropriate for replicating the erosion/redeposition physics associated with the magnetic sheath expected in ITER. The energy balance predicted by the B2 code indicated that about 50% of the input power reached the divertor plate, 35% was lost by atomic physics process (radiation and charge exchange), and 15% was lost by radial transport to the surrounding walls. These values reasonably well match those obtained in mirror machine experiments with ICRF heating. Changes in plasma parameters at longer length (to 25 m) and higher heating power (to 7 MW for ions and 2 MW of ECH) are under examination.

With the parameters predicted by the B2 code, estimates of the fusion rate in D/D plasmas can be made. In the baseline design (2 MW heating), the creation rate of neutrons, $\sim 10^6 / \text{s}$, is sufficiently low to permit continuous local operation of IDEAL without shielding. Unlike tokamaks, the IDEAL device also has negligible potential for creating MeV electrons and the associated hazard of intense x-ray emission.

VIII. Summary

The divertor plate design meets the minimum requirements for ITER. But the operating and safety margins are low. There are considerable uncertainties in the ITER operating characteristics which could eliminate those margins. Therefore, it is important to conduct well coordinated physics and technology R&D programs to reduce the uncertainties and resolve key issues. Such activities are planned.⁹ However, a much stronger emphasis will be required on SOL physics and engineering issues than has been applied previously in the fusion program.

Acknowledgements: We wish to thank the many scientists and engineers who contributed to the ITER design.

References

1. M. Leiser, Establishment of ITER: Relevant Documents, ITER Documentation Series No. 1, International Atomic Energy Agency, Vienna, 1988.
2. ITER Conceptual Design Activity Final Report, ITER Documentation Series No. 16, International Atomic Energy Agency, Vienna, 1991.
3. D.E. Post, K. Borrass, J.D. Callen, S.A. Cohen, et al., ITER Physics, ITER Documentation Series No. 21, International Atomic Energy Agency, Vienna, 1991.
4. ITER Conceptual Design Vol 1 & 2, ITER Documentation Series No. 3, International Atomic Energy Agency, Vienna, 1988.
5. S.J. Piet, K.A. McCarthy, D.F. Holland, et al., 14-th IEEE Symposium on Fusion Engineering, San Diego 1991, and EGG-M-91224.
6. M. Petravic, D. Heifetz, and D. Post, Jour. Nucl. Mater. 111 & 122, (1982) 294.
7. S.A. Cohen, K.A. Werley, D.E. Post, B.J. Braams, J.L. Perkins and D. Pearlstein, Jour. Nucl. Mater. 176 & 177, (1990) 909.
8. ITER Conceptual Design, ITER Documentation Series No. 18, International Atomic Energy Agency, Vienna, 1991.
9. Physics and Engineering Technology R&D for ITER Conceptual Design, ITER Documentation Series No. 19, International Atomic Energy Agency, Vienna, 1991.
10. V. Voitsenja and S.A. Cohen, Jour. Nucl. Mater. 176 & 177, (1990) 611.
11. K. Tani et al. ITER Reports, ITER-IL-Ph-1-9-J-1, ITER-IL-Ph-1-9-J-2, and ITER-IL-Ph-1-0-J-1.
12. B.J. Braams, Computational studies of Tokamak Equilibrium and Transport, Thesis, University of Utrecht, 1986.
13. K.A. Werley et al. , in Workshop on Edge Plasma Physics for BPX and ITER (1991).
14. T. Tsunematsu, K. Borrass, S. Cohen, F. Engelmann, et al. 13-th International Conference on Plasma Physics and Controlled Fusion Research, Washington, (1990), IAEA-CN-53/F-3-2.
15. S.A. Cohen, B.J. Braams, J. Brooks, J. Cummings, et al. 13-th International Conference on Plasma Physics and Controlled Fusion Research, Washington, (1990), IAEA-CN-53/F-3-3.

16. J. Laslo and W. Eckstien, Jour. Nucl. Mater. 184, (1991) 22.
17. J. Brooks, Jour. Nucl. Mater. 170 (1990) 164, J. Brooks, D. Brice, A Dewald, and R McGrath, J. Nucl. Mater. 162-164, (1989) 350, and J. Brooks ANL/FPP/TM-277 (1991).
18. J. Bohdanský, W. Eckstein, et al. Jour. Nucl. Mater. 111&112 (1982) 717, and J. Bohdanský (private communication).
19. M.J. Seaton, *Theory of Excitation by Electron Impact*, D.R. Bates, ed. (NY, Academic press 1962) and K.L. Bell, H.B. Gilbody, et al., CLM-R216 "Atomic and Molecular Data for Fusion", Culham Laboratory (1982).
20. H.D. Pacher and G.W. Pacher, ITER-IL-Ph-13-0-24, (1990).
21. J. Wesley, ITER Meeting, San Diego (July 1991).
22. M. Sugihara, ITER Meeting, San Diego, (July 1991).
23. S.K. Koh and R.I. Stephens, Fatigue and Fracture of Engineering Structures 14, 413 (1991).
24. K.N. Smith, P. Watson, and T.M. Topper, J. Materials 5, 767 (1970)
25. V.K. Thompson and W.J. Worraker, Fusion Engineering and Design 13, 187 (1990).
26. A. Kellman et al., Proc. 16-th Symposium on Fusion Techn., London (1990).
27. A. Russo, ITER-IL-Ph-8-0-26.
28. T. Sugie, K. Itami, H. Nakamura, et al. 13-th International Conference on Plasma Physics and Controlled Fusion Research, Washington, 1990, IAEA-CN-53/AV-4.
29. D. Hillis, K.H. Finken, J.T. Hogan, K.H. Dippel, et al., Phys. Rev. Lett. 65, (1990) 2382.
30. E.J. Synakowski, B.C. Stratton, P.C. Efthimion, R.J. Fonck, Phys. Rev. Lett. 65, (1990) 2255.
31. M.H. Redi and S.A. Cohen, Fusion Technology 20, (1991) 48.
32. M.H. Redi, S.A. Cohen, and E.J. Synakowski, PPPL-2765 and Nucl. Fusion (in press).
33. B.J. Braams, (private communication).
34. D.N. Ruzic, K.A. Werley, and S.A. Cohen, Jour. Nucl. Mater. 176&177, (1990) 926.
35. J.L. Perkins, J.D. Galambos, J.R. Gilleland, et al., LLNL Report UCRL-ID-104178 (1990) and J.L. Perkins, J.D. Galambos, and J.C. Wesley ITER-US-91-EN-SM-2 (1991)
36. W. Nevins, J. Wesley, D. Post et al. ITER Report (in press) (1991).
37. S.A. Cohen, PPPL-2788 (1991).
38. J. Brooks, R. Mattas, N. Hershkowitz, D. Smith, et al. ANL/FPP/TM-188 (1984).

Figure captions

1. Schematic drawing of the ITER device.
2. Section of the ITER plasma. A deuteron on the separatrix is shown impacting the divertor plate. The sputtered carbon atom is ionized a few mm from the divertor plate surface. The carbon ion's trajectory then follows another field line and impacts the divertor plate a short distance away in both the toroidal and poloidal directions.
3. Projection of the deuteron, carbon atom, and carbon ion trajectories in a vertical plane collinear with the tokamak major axis. Note that sputtered carbon atoms may leave the surface with a distribution of ejection angles. The tilt of the divertor plate with respect to the flux surface biases the ejected particle to step radially outward.
4. As in figure 3, projection of the carbon atom and carbon ion trajectories in a vertical plane collinear with the tokamak major axis. Here, the emphasis is to show the net transport of sputtered particles across the divertor plate.
5. Solid lines: Lifetime of a divertor plate as a function of $n_e w \tan \theta$ for a selection of plasma temperatures. Dotted and dashed lines: ratio of net lifetime to gross lifetime as a function of $n_e w \tan \theta$ for a selection of plasma temperatures. Although higher electron temperatures make redeposition more effective, the net lifetime is reduced.
6. Designs for the ITER divertor plates from the CDA. a) One divertor module (dimensions are in mm.) b) Carbon monoblock design, chosen for the physics phase. c) Tungsten tiles, chosen for the longer technology phase. Beryllium tiles (not shown) are considered as alternate backup options for both phases.
7. Strain range versus strain reversals to failure. Dramatically longer material lifetimes against fatigue failure occur at lower strain range values.
8. Qualitative comparison of several divertor designs. ITER has specified double-null configurations with 1.5 m deep divertors and pumping at the outside bottom, see a). Alternate configurations, such as in b) and c) may have superior divertor operating parameters because deeper divertors are predicted to have much lower plasma sheath temperatures and power flows. Additionally, changes in divertor shape, e.g., the reentrant design, can improve helium exhaust as well as increase energy loss by atomic processes.
9. A schematic view of the IDEAL linear plasma device for testing ITER divertor concepts, models and prototypes. Such a device could create the proper plasma parameters to perform credible tests of radiative divertors and gaseous neutralizers.

1- CENTRAL SOLENOID	5- PLASMA EXHAUST	9- FIRST WALL
2- SHIELD/BLANKET	6- CRYOSTAT	10- DIVERTOR PLATES
3- PLASMA	7- ACTIVE CONTROL COILS	11- POLOIDAL FIELD COILS
4- VACUUM VESSEL-SHIELD	8- TOROIDAL FIELD COILS	

Figure 1.

Figure 2.

Figure 3.

Figure 4.

Divertor Erosion/redeposition Net to Gross Lifetime Ratio

Figure 5.

a)

b)

c)

Figure 6.

Fatigue Lifetime

Figure 7.

Figure 8.

ITER Divertor Experiment and Laboratory: Phase 1

• Figure 9.

END

DATE
FILMED

4/10/92