**PRESSURE-INDUCED AMORPHIZATIONS OF SILICA ANALOGUES:
A PROBE OF THE RELATIONSHIP BETWEEN ORDER AND DISORDER**

Progress Report
for Period August 1, 1992-July 31, 1993

William S. Hammack
Department of Chemical Engineering
Carnegie Mellon University
Pittsburgh, Pennsylvania 15213

February 1993

Prepared for
THE U.S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-92ER45474

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

RECEIVED

FEB 19 1993

OSTI

MASTER

Abstract

Pressure-induced amorphizations of silica analogues: a probe of the relationship between order and disorder.

William S. Hammack
Department of Chemical Engineering
Carnegie Mellon University
Pittsburgh, PA 15213-3890

The purpose of my high pressure investigations is to determine the relationship between order and disorder in amorphous materials using high pressure techniques. Specifically, the experimental techniques used are high pressure x-ray diffraction, electron transmission microscopy, and Raman scattering. We have made two trips to the Cornell High Energy Synchrotron Source (CHESS) at Ithaca to measure x-ray diffraction patterns using Energy-Dispersive X-ray Diffraction (EDXD) techniques. There are three principal results at this point. (1) We have shown that the structural ordering in pressure-amorphized solids can be described as defects in curved-space. (2) High-resolution transmissions electron microscopy shown that pressure-amorphized alpha-quartz lacks periodicity at the atomic level. And (3) our study of a silicate mineral shows that pressure-induced amorphizations occur because of an impeded phase transition. At present we are measuring the Raman scattering for many of the systems studied at CHESS. This should result in several more publications by the end of the year. Lastly, we are investigating using CHESS and the Brookhaven synchrotron for further x-ray investigations

REPORT

J.M. Ziman begins his book *Models of Disorder* with the sentence: "Disorder is not mere chaos: it implies defective order". How defective this order can be is just beginning to be quantified: recently domains of order have been observed in glasses by neutron scattering and also crystalline solids have been turned into amorphous solids at ambient temperature by compression [1]. These latter transformations are sometimes reversible—when the pressure is released the amorphous state relaxes into its crystalline precursor, thus suggesting a close relationship between the disorder of these amorphous solids and the regularity of the crystalline solid. This observed "new order" makes cloudy some of the conventional distinctions between crystalline and noncrystalline solids. It is this relationship of order and disorder that we will probe in this proposal.

My previous work has focused primarily on the study of pressure-induced amorphization using *in situ* x-ray powder diffraction (XRD) and Raman spectroscopy. My research group has documented pressure-induced amorphizations and disorderings for several halide crystals, nitrates, and oxides. We have used these observations to suggest ordering schemes in halide glasses, ionic glasses, and amorphous molecular solids. Our most recent work explores several important aspects of solid-state amorphizations [2-7]. Our central experimental protocol is as follows: (a) apply hydrostatic pressures up to ~20.0 GPa to a crystalline solid, (b) follow the formation of an amorphous state by *in situ* Raman and x-ray diffraction measurements, and (c) release the pressure and observe the return of the crystalline state. Essentially we are asking the question "how much must a crystalline solid be rearranged to obtain an amorphous solid?" From our studies we have identified the central factors which control amorphizations: polytetrahedral ordering, ionicity, and connectivity of the structural units in the solids.

From the perspective of glass science, we are probing the medium range order (MRO) of the amorphous states formed—since the transformation is reversible we can surmise the structure of the amorphous state formed at high pressures (*vide infra*). MRO, as defined by Elliott, exists on the length scale of 5-20 Å; qualitatively MRO is any pattern used to connect various local atomic groupings. The determination of MRO is the major unresolved problem in the study of noncrystalline solids. Since noncrystalline solids have no long range order it is MRO which determines those properties which are of technological importance. As Angell has pointed out MRO controls: (1) the relaxation of stress within the glass, this is the fundamental phenomena underlying glass formation; and (2) nucleation of crystals in glasses, since nucleation in amorphous phases requires fluctuations extending over tens of Å—this is important in the formation and processing of glass ceramics. Also MRO controls (3) photochromism, (4) liquid-liquid phase separation, (5) diffusion and ionic conduction in glasses, and (6) the scattering of light.

The central difficulty in understanding MRO is finding experimental methods to probe it. MRO at a range of ~5 Å can be studied by Raman and NMR spectroscopies, but there are very few experimental techniques which can reveal MRO on the level of third and fourth neighbors; usually only theoretical work and computer simulations are used to investigate MRO. The relationship of the amorphous states formed at high pressures to glasses formed by melt-quenching at ambient pressure is the subject of our investigations.

First, we have a paper in press that shines light on a fundamental questions in glass science [8]. A central question in the study of amorphous materials is the extent to which they are ordered. When the crystalline intermetallic $R\text{-Al}_5\text{Li}_3\text{Cu}$ is compressed to 23.2 GPa, at ambient temperature, an amorphous phase is produced whose order can be described as defects in a curved-space crystal. The result supports a structural relationship between quasicrystals and amorphous metals based on icosahedral ordering. This also shows that a metallic crystal can be made amorphous by compression.

Second, we have determined that pressure amorphized materials are disordered at the same level as melt-quenched amorphous materials [9]. Alpha-quartz becomes x-ray amorphous when compressed, at ambient temperature, by pressures of 25 to 30 GPa. [Hemley, et al. *Nature* **334**, 5 (1988).] The relationship between pressure-amorphized and melt-quenched silica is of great interest. The most fundamental characteristic of melt-quenched silica is its lack of periodicity at the atomic level. We report, in this letter, that high-resolution electron microscopy shows that alpha-quartz, pressure-amorphized at 30.5 GPa is, as is conventional melt-quenched silica, amorphous at the atomic level.

Third, a central question in the study of pressure-induced amorphizations is why they occur. We have shown that the amorphizations are a result of an impeded phase transition [10]. Energy dispersive x-ray diffraction and Raman measurements show that the mineral wollastonite (CaSiO_3) becomes amorphous at a pressure of 25.6 GPa at 300 K. A consideration of the high pressure/high temperature behavior of CaSiO_3 shows that the amorphization occurs because the phase transition wollastonite perovskite CaSiO_3 is kinetically impeded. We suggest that the amorphous phase may be viewed as a defective long-period modulated wollastonite phase.

Lastly, we have several more results in preparation. (1) An extensive study of the amorphization of the alkali nitrates. (2) We have studied a series of cristobalite analogues. Their pressure responses provide insight into how crystal structures can be calculated ab initio.

REFERENCES

1. Amato, I., *A new order in glass*. Science, 1991. **252**: p. 1377.
2. Serghiou, G.C. and W.S. Hammack, *Pressure-induced crystalline-to-noncrystalline transformations of barium fluorozirconates: A probe of the medium range order of noncrystalline solids*. Journal of Chemical Physics, 1991. **95**: p. 5212-5223.
3. Serghiou, G.C. and W.S. Hammack, *Pressure-induced disordering in -SrZrF₆: Implications for the role of the counteraction in glassy SrZrF₆*. Journal of Chemical Physics, 1992. **96**: p. 6911-6916.
4. Serghiou, G.C., R.R. Winters, and W.S. Hammack, *Pressure-induced amorphization and reduction of T-Nb₂O₅*. Physical Review Letters, 1992. **68**: p. 3311-3314.
5. Serghiou, G.C., R.R. Winters, and W.S. Hammack, *Pressure-induced transformations of -BaZr₂F₁₀ and its relationship to glassy BaZr₂F₁₀*. Journal of Physics: Condensed Matter, 1992. **10**: p. 7627-7626.
6. Winters, R.R., G.C. Serghiou, and W.S. Hammack, *Observation and explanation of the reversible pressure-induced amorphization of Ca(NO₃)₂/NaNO₃*. Physical Review B, 1992. **46**: p. 2792-2797.
7. Hammack, W.S., G.C. Serghiou, and R.R. Winters, *Pressure-induced amorphization*, in *The Physics of Non-Crystalline Solids*, L.D. Pye, W.C. La Course, and H.J. Stevens, Editor. 1992, Taylor & Francis: London. p. 208-212.
8. Winters, R.R. and W.S. Hammack, *Pressure-induced amorphization of R-Al₅Li₃Cu: A structural relationship among amorphous metals, quasicrystals, and curved space*. Science, 1992. p. Accepted.
9. Winters, R.R., A. Garg, and W.S. Hammack, *High-resolution electron microscopy of pressure-amorphized-quartz*. Physical Review Letters, 1992. **69**: p. 3751-3753.
10. Serghiou, G.S. and W.S. Hammack, *Pressure-induced amorphization of wollastonite (CaSiO₃) at room temperature*. Journal of Chemical Physics, 1993. Submitted.

Reprints removed

END

**DATE
FILMED**

3 / 15 / 93