DOE/PC/79816--3

DOE/PC/79816--3

DE93 006467

Slurry Phase Fischer-Tropsch Synthesis:
Cobalt Plus a Water-Gas Shift Catalyst

Report for

October 1, 1988 to December 31, 1988

Report No.: DOE/PC79816-3

Contract No.: DE-AC22-87PC79816

by

Ian C. Yates

and

Charles N. Satterfield

for

U.S. Department of Energy

Pittsburgh Energy Technology Center

P.O. Box 10940-MS 920-L

Pittsburgh, PA 15236

Attention: V. Udaya S. Rao, Project Manager

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

NOTICE

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States nor any agency thereof, nor any of their employees, makes any warranty, expressed or implied or assumes any legal liability or responsibility for any third party's use or the results of such use of any information, apparatus, product or process disclosed in this report, or represents that its use by such third party would not infringe privately owned rights.

Summary

A "classical" cobalt Fischer-Tropsch catalyst (Co/MgO/silica) was reduced and slurried in our reactor in combination with a previously-reduced Cu/ZnO/Al₂O₃ water-gas-shift catalyst. The combined catalyst system was run at fixed process conditions for more than 400 hours. The system showed stable selectivity. In particular, the Cu/ZnO/Al₂O₃ water-gas-shift catalyst remained reasonably active in the presence of the cobalt catalyst.

The hydrocarbon selectivity of the cobalt and Cu/ZnO/Al₂O₃ catalyst system compared very favorably to the selectivity of iron-based catalysts similar to those used at SASOL. Methane selectivity was slightly higher for the cobalt-based system, but C₅⁺ selectivity was essentially the same. The hydrocarbon product distribution appeared to exhibit a double- α behavior. α_1 was near 0.80 which is higher than that of iron catalysts, while α_2 was calculated to be 0.86 which is somewhat lower than would be typical for an iron-based catalyst.

The cobalt Fischer-Tropsch catalyst deactivated with time-on-stream. Further experiments, particularly examining the activity and selectivity of the cobalt catalyst alone, are necessary to determine conclusively the causes of this deactivation.

Outline

	Page
1. Introduction	.1
2. Cobalt and Cu/ZnO/Al ₂ O ₃ combined	.2
2.1 Experimental	.2
2.2 Results and Discussion	.4
2.2.1 Start-up.	.4
2.2.1.1 Start-up Activity.	.5
2.2.1.2 Start-up Selectivity	.6
2.2.2 Water-Gas-Shift Activity.	.8
2.2.3 Fischer-Tropsch Selectivity	.11
2.2.4 Fischer-Tropsch Activity.	.14
3. Conclusions.	.15
4. Future Work.	.16
5. References	.17

1. Introduction

As discussed in our previous status reports, we have found a $\text{Cu/ZnO/Al}_2\text{O}_3$ low-temperature shift catalyst that maintains suitable activity in our slurry reactor system. The tests on this water-gas-shift catalyst were performed in the absence of a cobalt Fischer-Tropsch catalyst and were designed to provide us with reliable information on the intrinsic behavior of low-temperature shift catalysts in our slurry reactor.

In this report, we discuss some results from experiments in which the $\text{Cu/ZnO/Al}_2\text{O}_3$ catalyst was combined with a "classical" promoted cobalt on SiO_2 catalyst. The selectivity of the combined catalyst system is compared to potassium-promoted precipitated and potassium-promoted fused iron catalysts similar to those used at SASOL.

2. Cobalt and Cu/ZnO/Al₂O₃ combined

The Cu/ZnO/Al₂O₃ shift catalyst was run on its own for more than 1000 hours at a variety of different process conditions. The details of this run have been presented previously.

A cobalt Fischer-Tropsch catalyst was reduced externally and then added to the slurry. The combined system was then allowed to operate at constant process conditions for more than 400 hours. The intent of these experiments was to determine the feasibility of the combined catalyst system. This was considered to be especially important in light of the rapid deactivation of the water-gas-shift catalyst that has been reported by previous researchers studying a combination of a cobalt Fischer-Tropsch and a water-gas-shift catalyst (Union Carbide 1984a, 1984b, and 1984c; Tominaga et al., 1987). Detailed results on this run are presented below.

2.1 Experimental

The cobalt catalyst used is a Co/MgO on a low-Al₂O₃ SiO₂. This catalyst was prepared for us by an outside laboratory and is of the approximate composition of the cobalt catalysts used at Ruhrchemie (Storch et al., 1951).

Supplied as an extrudate, the catalyst was ground and sieved to 50 to 90 μ m (170 to 270 ASTM Mesh). Before reduction, the sieved catalyst was calcined in air at 130°C for 24 hours to remove any water and/or volatile impurities. During calcination the sample lost approximately 4 % of its weight and underwent a color change from a purple/brown to

grey. This color change is most probably associated with loss of water of hydration.

Following calcination, 25 grams of the catalyst were placed in a reduction tube. The catalyst was held in the reduction tube with a small piece of glass wool and hydrogen flow (prepurified, MedTech Gases, Inc.) was increased to 2 Nl/min (approximately 10,000 V/V/hr). At this flow rate, the pressure in the reduction tube was 0.79 MPa (100 psig). The temperature of the reduction tube was increased steadily from 25°C to 360°C over 8 hours while both pressure and flow rate were kept approximately constant. The reduction unit was then held at 360°C for 16 hours. The catalyst lost 28 wt.% during reduction. The reduced catalyst was added to the reactor which was being held under helium and contained the reduced Cu/ZnO/Al₂O₃ (25 grams unreduced weight of Katalco, Inc. 52-2) slurried in octacosane (400 grams, Humphrey Chemical, Inc.).

The reactor was then brought on-stream at 0.79 MPa (100 psig), 240°C, and H₂/CO=1.5 at a flow rate of 0.5 Nl/min. The CO used in these experiments was CP grade (Granite State Oxygen, Inc.) and the H₂ was prepurified grade (MedTech Gases, Inc.). Initial flow measurements after two and three hours-on-stream indicated that greater than 90 percent flow contraction was occurring. This would correspond to almost complete conversion. Under these high conversion conditions, it was feared that the catalysts might be subjected to overly reducing or carbiding conditions, caused by the depletion of one or both of the reactants. In order to avoid the potential detrimental effects on the catalysts of running at this high conversion, the reactor conditions

were changed after 4 hours-on-stream.

The new conditions were 0.79 MPa, 240°C, and $H_2/CO=1$ at a flow rate of 1.0 Nl/min. Because little is known about the long-term stability of this type of combined catalyst system (Union Carbide 1984a, 1984b, and 1984c; Tominaga et al., 1987), we chose to hold these conditions constant for the duration of the run.

During the crucial start-up period, the flow rate and composition of the volatile products were measured at frequent intervals. No attempt was made to monitor the condensed liquid products, as these were probably not representative of the synthesized products (Huff and Satterfield, 1984a; Huff and Satterfield, 1985; Matsumoto and Satterfield, 1989). The reactor system and analytical techniques used here have been described previously (Huff et al., 1983; Matsumoto, 1987).

Following the start-up period, five complete material balances, in which liquid products were trapped and analyzed, were performed. All five material balances closed to within 3% on oxygen, which was chosen as the material balance closure criteria because carbon and hydrogen accumulate in the reactor in the form of high molecular weight hydrocarbons (Huff, 1982; Donnelly et al., 1988).

2.2.1 Start-up

During the first 60 hours-on-stream, fourteen flow measurements, non-condensable gas analyses (RGA), and light gas analyses (HP 5880) were made. Because these were not part of complete material balances, the analyses of the GCs cannot be tied together. However, when taken

separately, these analyses provide us with valuable information on both the activity and selectivity of the combined catalyst system during the start-up period.

2.2.1.1 Start-up Activity

The flow and composition data are presented in Table 1. By combining the flow measurements with the non-condensable gas analyses, the conversion, $-X_{H_2 + CO}$, and H_2/CO usage ratio, $-R_{H_2}/-R_{CO}$, can be determined. Figure 1 shows the start-up conversion for the first 60 hours-on-stream. The first data point may represent transience resulting from the higher conversion part of the run, the first 4 hours. Except for this first data point, the figure clearly indicates that, at least for the start-up period, the activity of the catalyst system for total synthesis gas consumption is essentially constant.

Figure 2 shows the H_2/CO usage ratio of the catalyst system during the start-up. The H_2/CO usage ratio represents the ratio of consumed hydrogen to consumed carbon monoxide. In the absence of the water-gas-shift reaction, the H_2/CO usage ratio would be near two, the same as that of the synthesized hydrocarbons; with the water-gas-shift reaction at or close to equilibrium, the H_2/CO usage ratio would be nearer to 0.5. There are, therefore, two important conclusions to be drawn from Figure 2. First, because the H_2/CO usage ratio is near one, it is clear that the water-gas-shift catalyst has retained some of its activity. Second, the water-gas-shift catalyst does not appear to be deactivating during the start-up period.

These results are in contrast to low activity and rapid

deactivation of water-gas-shift catalysts observed under similar reaction conditions by Union Carbide (1984a, 1984b, and 1984c) and Tominaga and co-workers (1987).

2.2.1.2 Start-up Selectivity

By examining the light gas GCs taken on the HP 5880, three important parameters can be calculated: α_1 , 1-butene/n-butane, and 2-butene/1-butene. These selectivity results are presented in Table 3.

The calculation of the first chain growth probability, α_1 , from linear regression of C_3 - C_7 products has been shown to be an appropriate approximation by Donnelly et al. (1988) and, in more detail, by Matsumoto and Satterfield (1989). At this point in the run, higher molecular weight products, which are condensed in the traps, are probably not representative of the products being synthesized and must therefore be excluded from these analyses.

Figure 3 shows a typical light gas Schulz-Flory diagram from a sample taken after 22 hours-on-stream. The line is the best-fit linear regression of the total C_3 - C_7 products and α_1 is calculated to be 0.81. However, the logarithms of the normalized mole fractions are not fit extremely well by the line. The C_3 products fall below the line. For iron, this is normally observed with only the C_2 products (Huff and Satterfield, 1984a). With C_7 products also beginning to "tail off" as a result of vapor-liquid equilibrium in the 1°C cold trap, this estimated value of α_1 represents a lower bound.

The phenomenon of the C_3 products lying below the linear regression line was observed on all Schulz-Flory plots for this

catalyst system, even up through 250 hours-on-stream. Therefore, it can not be explained as transient behavior. Lower production of methane and light gas products, C_2 - C_4 , is a substantial selectivity improvement as it represents higher rates of synthesis of desired products: gasoline, diesel fuel, and wax products. The overall hydrocarbon selectivity of this catalyst is compared in detail to other Fischer-Tropsch catalysts below (see section 2.2.3). Figure 4 shows the linearly-regressed values of α_1 remain relatively constant with time-on-stream. The values of α_1 range between 0.80 and 0.86.

The selectivity of the catalysts to alkanes and various alkenes is also examined in detail. The analyses show that, at a given carbon number, alkanes are produced in the greatest concentration, followed by 2-alkenes, 1-alkenes and lastly n-alcohols. Figure 5 shows the ratios of 1-alkene/n-alkane and 1-alkene/2-alkane both decrease with increasing carbon number up to C_{10} .

1-Alkenes are reported to be the predominant primary product of the Fischer-Tropsch synthesis on both cobalt and iron (Pichler and Schulz, 1970; Schulz et al., 1970), with alkanes and internally-bonded alkenes being mostly produced by hydrogenation and isomerization, respectively. Therefore, these secondary reactions, hydrogenation and isomerization, take place to a much greater extent on longer hydrocarbon chains, perhaps because of their increased residence time in the reactor. The increase of secondary reactions at higher carbon number has been reported previously on cobalt catalysts by a number of researchers including Pichler et al. (1967) and Schulz (1983).

The C_4 products are chosen to be qualitatively representative of

the overall alkene-alkane selectivity of the system because they are not condensed in either of the product traps and can be reliably resolved on the GC. The use of C₄ products for the analysis of hydrogenation and isomerization is discussed in detail by Donnelly and Satterfield (1989). Figure 6 shows the 1-Butene/n-Butane and 1-Butene/2-Butene ratios for the first 60 hours of the run. It can be seen that, after an initial "levelling out" period, both ratios decrease slightly and then approach constant values.

With the selectivity and activity apparently close to steady state, a series of five material balances was performed during the next 175 hours-on-stream. Material balances provide data on the production of liquid products, in particular water and high molecular weight hydrocarbons. The reactor was left on-stream for a total of 405 hours to allow for a reliable analysis of the slurry composition.

2.2.2 Water-gas-shift Activity

Water is produced as a byproduct of the primary synthesis (Anderson, 1980) and can subsequently react with CO to produce H₂ and CO₂ via the water-gas-shift reaction:

Knowledge of the relative rates of production of H₂O and CO₂ provides information on the intrinsic water-gas-shift activity of the system.

At the temperatures of interest for the Fischer-Tropsch synthesis the equilibrium of the water-gas-shift reaction lies far to the right, favoring the production of H₂ and CO₂ (Moe, 1962; Newsome, 1980). Thus, a good measure of the water-gas-shift activity is the extent to

which H_2O reacts to form CO_2 as measured by:

$$X_{\text{WGS}} = P_{\text{CO}_2} / (P_{\text{CO}_2} + P_{\text{H}_2\text{O}}). \quad (2)$$

This parameter, X_{WGS} , is independent of total synthesis gas consumption by the Fischer-Tropsch reaction, as it depends solely on the relative rates of production of CO_2 and H_2O . Because we are working with a well-mixed system of uniform composition, the relative rates of production of all components are related directly to their measurable partial pressures.

Figure 7 shows the extent of water-gas-shift, expressed as shown in equation 2, for the five material balances performed. The water-gas-shift catalyst clearly retains its activity. Cobalt is known to have no intrinsic water-gas-shift activity (Storch et al., 1951; Anderson, 1980) and, therefore, the water-gas-shift activity is presumed to come from the $\text{Cu/ZnO/Al}_2\text{O}_3$ catalyst.

This is the first time that data showing stable activity of a water-gas-shift catalyst which was being used in conjunction with a Fischer-Tropsch catalyst have been reported. In their patents, Post and co-workers (Post et al., 1985a and 1985b) presented no time-on-stream data on the water-gas-shift activity of their combined shift and Fischer-Tropsch catalyst system which they operated in a fixed-bed.

Also working in a fixed-bed, researchers at Union Carbide (Union Carbide 1984a, 1984b, and 1984c) attempted a number of experiments in which they combined a cobalt on a proprietary support catalyst with copper-based shift catalysts. All catalysts used in these runs were prepared by Union Carbide. In all of their experiments, they observed rapid deactivation of the shift catalysts, which they attributed to a

number of causes including poisoning and competitive adsorption by alkenes. Examination of the details of operation reveals two other potential causes. First, the copper-based catalysts may have been incorrectly prepared. Specifically, obtaining a fine dispersion of copper on the surface of the shift catalyst is reported to be crucial (Campbell, 1970; Young and Clark, 1970). This can be greatly influenced by the method of precipitation, particularly the pH of the precipitating solution (Campbell, 1970).

Recently, Tominaga, Miyauchi and Fujimoto (1987) reported results of work performed with 10 wt% Co on SiO_2 combined with a $\text{Cu/Cr}_2\text{O}_3$ as a water-gas-shift catalyst. They operated in a fixed-bed at 3 atm and between 220 and 280°C.

The water-gas-shift catalyst was run alone for 24 hours and is reported to have maintained complete H_2O conversion of a 25 mole percent H_2O in CO feed. The primary focus of this research was to study the Kölbel-Engelhardt synthesis. In the Kölbel-Engelhardt synthesis, CO and H_2O , rather than synthesis gas, are fed to the reactor. However, some data are reported on feeds containing only H_2 and CO with a H_2/CO ratio of 0.5. Two trends are observed from these runs. First, when the water-gas-shift catalyst is added, the mole percent of CO_2 in the products increases from 0.1 to 6.0, indicating a large enhancement in water-gas-shift activity. Second, the weight fraction of C_5^+ products remains unaffected by addition of the water-gas-shift catalyst to the system.

Tominaga and co-workers report that the yield of CO_2 , which is a measure of the water-gas-shift activity, decreased to 50% of its

initial value within the first 6 hours of operation. They postulated that this results from covering of the active sites on the shift catalyst by high boiling hydrocarbons, but provide no direct evidence to support their claim. They then state that this 50% of initial activity is the steady-state value, but present no data after 12 hours-on-stream.

2.2.3 Fischer-Tropsch Selectivity

The products of the Fischer-Tropsch synthesis are primarily linear hydrocarbons distributed over a wide range of carbon numbers. This hydrocarbon product distribution has been described as a polymerization mechanism in which single-carbon units are added to growing chains (Herrington, 1946; Anderson et al., 1951). The mathematical model of this type of polymerization was developed independently by Schulz (1935) and Flory (1936). In its simpler form, the model suggests that a semilogarithmic plot of mole fraction of product as a function of carbon number should produce a straight line with a slope characteristic of the chain growth probability, α . Such a semilogarithmic plot is often referred to as a Schulz-Flory diagram. A number of researchers have observed a "break" in the Schulz-Flory plot at around C_{10} (on iron: Konig and Gaube, 1983; Huff and Satterfield, 1984a; Schliebs and Gaube, 1985; Dictor and Bell, 1986; on cobalt: Schulz et al., 1982; on ruthenium: Inoue et al., 1987), leading many to conclude that more than one chain growth probability exists.

Figure 8 shows a semilogarithmic plot of total mole fraction of product versus carbon number for the five of the material balances.

The system retains stable selectivity and the experiments were very repeatable. Although the so-called "break" is not pronounced because the value of α_1 is very near the value of α_2 , it is reasonably clear that the system exhibits a double- α . A slight increase in higher molecular weight products with time-on-stream can also be observed, indicating that early runs may not represent vapor-liquid equilibrium.

Figure 9 shows a plot of the C_3 to C_{18} products from material balance 4 fit by a double- α regression which was developed by Donnelly et al. (1988). The values of α_1 and α_2 were calculated by non-linear regression to be 0.77 and 0.84 respectively. It can be seen that the C_3 products again lie below the regression line as was observed in the start-up.

The selectivity of this material balance was taken to be representative and was compared to the selectivity of a potassium-promoted, precipitated iron catalyst, the Ruhrchemie catalyst, and a potassium-promoted fused magnetite catalyst, C-73. The precipitated iron catalyst was formerly used at SASOL and is similar to that currently used in their fixed-bed units; SASOL uses a fused magnetite catalyst of unknown composition in their entrained-bed synthesis. The C-73 catalyst is a triply-promoted fused magnetite catalyst which is manufactured for ammonia synthesis. No optimization of the composition of this fused magnetite catalyst for the Fischer-Tropsch synthesis has been performed.

Table 3 shows the selectivity comparison. The combined catalyst system has a number of very favorable selectivity characteristics. First, although the methane yield is substantial, the yield of light

gases is very much lower than the other two catalysts. If the total lighter-than-gasoline products, ΣC_1-C_5 , are compared, the combined cobalt and water-gas-shift catalyst system produced 23.1 wt.% of this fraction, which is slightly higher than the Ruhrchemie, 20.8 wt.%, but much lower than the C-73, 48.3 wt.%. The gasoline range, ΣC_5-C_{12} , yield of the cobalt-based catalyst system was superior, while the diesel selectivity, $\Sigma C_{13}-C_{19}$, was comparable to the Ruhrchemie and higher than the C-73. Wax yield, $\Sigma C_{20}-C_{30}$, was slightly lower for the cobalt catalyst system than the Ruhrchemie, but was still substantially higher than the C-73.

Apart from the overall hydrocarbon selectivity, two additional selectivity parameters were examined. First, oxygenate selectivity was studied. Oxygenate yield is important because oxygenates must be removed from the final product. As can be seen from Table 4, the cobalt and water-gas-shift catalysts exhibited a far lower selectivity to oxygenates than did either of the iron-based catalysts.

Second, the molar 1-butene/n-butane ratio of the three catalyst systems was compared. With 1-alkenes the predominant primary product, this parameter is a measure of the hydrogenation activity of the catalyst; the lower the 1-butene/n-butane ratio the more active the catalyst is for hydrogenation. From the selectivity information, it is evident that the cobalt and water-gas-shift catalyst system has a much higher hydrogenation activity than the iron-based catalysts. This low 1-alkene/n-alkane ratio is characteristic of cobalt catalysts (Pichler et al., 1967; Schulz, 1983). However, earlier work with 1-butene fed to the $Cu/ZnO/Al_2O_3$ catalyst on its own indicated that it also had some

hydrogenation activity. Further experiments are needed to determine precisely the source of the hydrogenation activity.

To get more information on the hydrogenation and isomerization activity of the catalyst system component Schulz-Flory diagrams were also examined. Figure 10 shows a component Schulz-Flory diagram for material balance 4 which was performed after 189 hours-on-stream. This provides additional information on the selectivity of the system to 1-alkenes, n-alkanes, as well as 2-alkenes and n-alcohols. As indicated by the low 1-alkene/n-alkane ratio, the n-alkanes are seen to be the principle product, followed by 2-alkenes, 1-alkenes and lastly n-alkanes. 1- and 2-alkenes appear to follow a single- α distribution which may be due to the fact that they are hydrogenated to alkanes more readily at higher carbon numbers, rather than because of intrinsic chain growth mechanisms.

Figure 11 shows a semilogarithmic plot of relative mole fraction of products from the slurry wax versus carbon number. The data at carbon numbers 32, 44, and 46 were removed from the analysis because impurities were discovered at these carbon numbers in the original octacosane charge. From the linear regression of this plot, α_2 is calculated to be 0.86. This is higher than the value of α_1 of 0.8 to 0.83 as calculated by linear regression which is further evidence that the products follow a double- α distribution.

2.2.4 Fischer-Tropsch Activity

In the above sections, we have presented only selectivity information on the combined catalyst system. The selectivity of the

two catalysts is seen to compare very favorably with that of iron-based catalysts. Unfortunately, however, the cobalt catalyst deactivated with time-on-stream. Figure 12 shows a plot of the rate of total synthesis gas consumption divided by the partial pressure of hydrogen versus time-on-stream. This plot shows the two-fold decrease in the rate of synthesis gas consumption. This may have been caused by carbiding of the catalyst that resulted from operation above optimum temperature or by contacting of the cobalt catalyst with the Cu/ZnO/Al₂O₃ catalyst. Further experiments, particularly examining the behavior of the cobalt catalyst on its own, are necessary to determine conclusively the cause of this deactivation.

3. Conclusions

A. The cobalt catalyst was reduced and combined with the already reduced Cu/ZnO/Al₂O₃. The combined catalyst system showed stable selectivity.

B. The Cu/ZnO/Al₂O₃ water-gas-shift catalyst remained active even in the presence of the cobalt catalyst. Approximately 40 mole percent of the water which was synthesized was converted to hydrogen via the water-gas-shift reaction.

C. The selectivity of the cobalt and Cu/ZnO/Al₂O₃ catalyst system compared very favorably to the selectivity of iron-based catalysts similar to those currently in use at SASOL. Methane selectivity was slightly higher for the cobalt-based system, but C₅⁺ selectivity was essentially the same.

D. The cobalt Fischer-Tropsch catalyst deactivated with time-on-stream. Further experiments, particularly examining the behavior of the cobalt catalyst on its own, are necessary to determine conclusively the cause of this deactivation.

4. Future Work

We next plan to run the cobalt catalyst alone. This will develop a "base-line" to which we can compare the activity and selectivity of the combined cobalt and $\text{Cu/ZnO/Al}_2\text{O}_3$ catalyst system. Particular attention will be given to understanding the causes of deactivation of the cobalt catalyst and determining ways to ensure stable activity of this catalyst in our slurry reactor. In addition, secondary reactions of the cobalt catalyst will also be studied in detail.

References

- Agrawal, P. K., Katzer, J. R. and Manogue, W. H., J. Cat., 69, 327-344 (1981).
- Anderson, R.B., The Fischer-Tropsch Synthesis, Academic Press Inc., Orlando, 1984.
- Anderson, R.B., Friedel, R.A., Storch, H.H., J. Chem. Phys., 19, 313 (1951).
- Beuther, H., Kibby, C.L., Kobylinski, T.P., and Pannell, R.B., United States Patent 4,399,234, August 16, 1983.
- Beuther, H., Kibby, C.L., Kobylinski, T.P., and Pannell, R.B., United States Patent 4,413,064, November 1, 1983.
- Borghard, W.G., and Bennett, C.O., Ind. Eng. Chem. Proc. Res. and Dev., 18, 18 (1979).
- Campbell, J.S., Ind. Eng. Chem. Process Des. Dev., 9, 588 (1970).
- Dent, A.L., and Lin, M., Adv. Chem. Ser., 178, 47 (1979).
- Dictor, R.A., and Bell, A.T., J. Catal., 97, 121 (1986).
- Donnelly, T.J., and Satterfield, C.N., Appl. Catal., in press (1989).
- Donnelly, T.J., Yates, I.C., and Satterfield, C.N., Energy Fuels, 2, 734 (1988).
- Dry, M.E., Appl. Ind. Catal., 2, 167 (1983).
- Flory, P.J., J. Am. Chem. Soc., 58, 1877 (1936).
- Fu, L., Rankin, J.L., Bartholomew, C.H., Cl Mol. Chem., 1, 369 (1986).
- Hanlon, R.T., Catalyst Characterization and Secondary Reaction Effects in Iron-Catalyzed Fischer-Tropsch Synthesis, Sc. D. Thesis, Massachusetts Institute of Technology (1985).
- Herrington, E.F.G., Chem. Ind. (London), 65, 346 (1946).
- Huff, G. A., Fischer-Tropsch Synthesis in a Slurry Reactor, Sc. D. Thesis, Massachusetts Institute of Technology (1982).
- Huff, G.A., Jr., and Satterfield, C.N., Ind. Eng. Chem. Fund., 21, 479 (1982).
- Huff, G.A., Jr., Satterfield, C.N., and Wolf, M.H., Ind. Eng. Chem. Fund., 22, 259 (1983).

- Huff, G.A., Jr., Satterfield, C.N., J. Catal., **85**, 370 (1984a).
- Huff, G.A., Jr., Satterfield, C.N., Ind. Eng. Chem. Process Des. Dev., **23**, 696 (1984b).
- Huff, G.A., Jr., Satterfield, C.N., Ind. Eng. Chem. Process Des. Dev., **24**, 986 (1985).
- Inuoe, M., Miyake, T., and Inui, T., J. Catal., **105**, 266 (1987).
- Kibby, C. L., Pannell, R. B., and Kobylinski, T. P., A.C.S. Pet. Chem. Preprints, **29** (4), 1113 (1984).
- Konig, L., and Gaube, J., Chem.-Ing. Tech., **55**, 14 (1983).
- Lu, D.C., A Kinetic Study of the Modified Fischer-Tropsch Synthesis over an Alumina-Supported Cobalt Oxide Catalyst, Ph.D. Thesis, Arizona State University, 1985.
- Matsumoto, D.K., The Effects of Selected Process Variables on the Performance of an Iron Fischer-Tropsch Catalyst, Sc. D. Thesis, Massachusetts Institute of Technology (1987).
- Matsumoto, D.K., and Satterfield, C.N., Energy Fuels, in press (1989).
- Moe, J.M., Chem. Eng. Prog., **58**(3), 33 (1962).
- Newsome, D.S., Catal. Rev-Sci. Eng., **21**(2), 275 (1980).
- Pichler, H., and Schulz, H., Chem.-Ing. Tech., **42**, 1162 (1970).
- Pichler, H., Schulz, H., and Elstner, M., Brennst.-Chem., **48**, 3 (1967).
- Rautavuoma, A and van der Baan, H. S., Appl. Cat., **1**, 247 (1981).
- Reuel, R.C. and Bartholemew, C.H., J. Catal., **85**, 78 (1984).
- Roper, M., Hemmerich, R., and Keim, W., Ger. Chem. Eng., **7**, 329 (1984).
- Sarup, B., and Wojchiechowski, B.W., Can. J. Chem., **62**, 240 (1984).
- Satterfield, C.N., Mass Transfer in Heterogeneous Catalysis, Krieger Publishing, Florida, 1970.
- Satterfield, C.N., Heterogeneous Catalysis in Practice, McGraw-Hill Publishing, New York, 1980.
- Schulz, G.V., Z. Phys. Chem. Abt. B, **30**, 379 (1935).
- Schulz, H., Plenary Lecture held at 5 th International Conference on Heterogeneous Catalysis, October 3-4, 1983, Varna, Bulgaria.

Schulz, H., Report to the German Government, BMFT-FB-T 80-124, November 1980.

Schulz, H. Rao, B.R., Elstner, M., Erdol und Kohle, 23, 651 (1970).

Schliebs, B. and Gaube, J., Ber. Bunsenges Phys. Chem., 89, 68 (1985).

Shah, Y.T., and Perrotta, P.J., Ind. Eng. Chem. Prod. Res. Dev., 15, (1976).

Slack, A.V., and James, G.R., Ammonia, Dekker, New York (1974-1977).

Storch, H.H., Anderson, R.B., Hofer, J., Hawk, C., Anderson, H., and Golumbic, N., Synthetic Liquid Fuels from Hydrogenation of Carbon Monoxide, United States Bureau of Mines, Technical Paper No. 709 (1948) and Bulletin 578 (1959).

Storch, H.H., Golumbic, N., and Anderson, R.B., The Fischer-Tropsch and Related Syntheses, Wiley, New York, 1951.

Tominaga, H., Miyachiharu, M. and Fujimoto, K., Bull. Chem. Soc. Jpn., 60, 2310 (1987).

Union Carbide Corporation (Tarrytown Technical Center, Tarrytown, New York), Liquid Hydrocarbon Fuels from Syngas, Technical Progress Report DE-AC22-81PC40077, Third Annual Report, March, 1983-February, (1984a).

Union Carbide Corporation (Tarrytown Technical Center, Tarrytown, New York), Liquid Hydrocarbon Fuels from Syngas, Technical Progress Report DE-AC22-81PC40077, Thirteenth Quarterly Report, March, 1984-May, (1984b).

Union Carbide Corporation (Tarrytown Technical Center, Tarrytown, New York), Liquid Hydrocarbon Fuels from Syngas, Technical Progress Report DE-AC22-81PC40077, Fifteenth Quarterly Report, August, 1984-September, (1984c).

Vanhove, D., Zhuyong, Z., Makambo, L., and Blanchard, M., Appl. Catal., 9, 327 (1984).

Wang, J., Physical, Chemical, and Catalytic Properties of Borided Cobalt Fischer Tropsch Catalysts, Ph.D. Thesis, Brigham Young University, 1987.

Yang, C-H., Massoth, F.E., and Oblad, A.G., Adv. Chem. Ser., 178, 35 (1979).

Yates, I.C., Satterfield, C.N., Ind. Eng. Chem. Res., in press.

Young, P.W., and Clark, C.B., Chem. Eng. Prog., 69(5), 69 (1970).

Zhang, X., Fischer-Tropsch Synthesis over Cobalt Catalysts: A Study with Isotopic Methods, Ph.D. Thesis, University of Pittsburgh, 1986.

START-UP ACTIVITY FOR Co/ACS-1

Table 1

DATE	TIME	TDS hours	SAMPLE	Q in NI/min	12/COin	Q out NI/min	12	Outlet Concentrations (Measured by RGN)	CO	CO2	CO2/6	X 12	X CO	X TOT	R CO2 mol/min	Usage Ratio
04 OCT	16:30	5.00	2	1.000	1.0	0.438	33.334	3.194	36.360	26.635	0.204	0.700	0.681	0.694	5.213	1.039
05 OCT	07:30	20.50	3	1.000	1.0	0.507	36.799	2.390	40.450	19.092	0.241	0.627	0.590	0.600	4.504	1.063
05 OCT	09:00	22.00	4	1.000	1.0	0.502	36.313	2.343	40.932	19.820	0.200	0.635	0.589	0.612	4.443	1.079
05 OCT	11:00	24.00	5	1.000	1.0	0.504	37.102	2.340	40.648	19.151	0.206	0.625	0.590	0.607	4.312	1.059
05 OCT	12:30	25.50	6	1.000	1.0	0.509	37.306	2.363	40.055	19.049	0.267	0.620	0.584	0.602	4.324	1.060
05 OCT	14:00	27.00	7	1.000	1.0	0.494	37.567	2.330	40.600	19.056	0.235	0.629	0.599	0.614	4.201	1.050
05 OCT	16:30	29.50	8	1.000	1.0	0.503	37.696	2.250	40.928	10.660	0.244	0.620	0.588	0.604	4.196	1.055
05 OCT	19:00	32.00	9	1.000	1.0	0.507	37.702	2.258	41.176	10.346	0.231	0.617	0.582	0.599	4.156	1.059
05 OCT	22:00	35.00	9.2	1.000	1.0	0.500	38.046	2.226	41.357	17.929	0.233	0.620	0.586	0.603	4.002	1.056
06 OCT	00:00	45.00	9.3	1.000	1.0	0.517	38.057	2.179	42.721	16.603	0.242	0.607	0.559	0.583	3.830	1.006
06 OCT	09:30	46.50	10	1.000	1.0	0.509	37.990	2.205	42.819	16.711	0.238	0.613	0.564	0.589	3.790	1.007
06 OCT	12:00	49.00	11	1.000	1.0	0.511	39.044	2.133	42.023	16.405	0.202	0.601	0.571	0.586	3.742	1.053
06 OCT	14:15	51.25	12	1.000	1.0	0.506	39.260	2.195	41.643	16.476	0.220	0.603	0.578	0.590	3.723	1.042
06 OCT	17:00	54.00	13	1.000	1.0	0.491	39.307	2.132	41.857	16.211	0.225	0.613	0.589	0.601	3.555	1.041
06 OCT	21:00	58.00	14	1.000	1.0	0.409	39.219	5.152	42.407	15.791	0.239	0.616	0.585	0.600	3.450	1.05

Table 2

Start-up Selectivity for Cobalt and Water-Gas-Shift Catalyst System.

START-UP SELECTIVITY FOR Co/WGS-1

DATE	TIME	TOS hours	SAMPLE	Q in Nl/min	H ₂ /CO in	Q out Nl/min	Alpha 1	1-butene/ n-butane	1-butene/ 2-butene
04 OCT	15:30	5.00	2	1.000	1.0	0.438	0.80	0.38	0.58
05 OCT	07:30	20.50	3	1.000	1.0	0.507	0.81	0.58	0.71
05 OCT	09:00	22.00	4	1.000	1.0	0.502	0.81	0.57	0.70
05 OCT	11:00	24.00	5	1.000	1.0	0.504	0.84	0.57	0.70
05 OCT	12:30	25.50	6	1.000	1.0	0.509	0.83	0.56	0.69
05 OCT	14:00	27.00	7	1.000	1.0	0.494	0.81	0.56	0.69
05 OCT	16:30	29.50	8	1.000	1.0	0.503	0.85	0.55	0.69
05 OCT	19:00	32.00	9	1.000	1.0	0.507	0.81	0.55	0.69
06 OCT	09:30	46.50	10	1.000	1.0	0.509	0.81	0.55	0.68
06 OCT	12:00	49.00	11	1.000	1.0	0.511	0.85	0.54	0.68
06 OCT	14:15	51.25	12	1.000	1.0	0.506	0.84	0.53	0.67
06 OCT	17:00	54.00	13	1.000	1.0	0.491	0.81	0.53	0.67
06 OCT	21:00	58.00	14	1.000	1.0	0.489	0.82	0.53	0.68

Table 3

Selectivity Comparison of Cobalt and Water-gas-shift Catalyst with Iron Catalysts

EXPERIMENTAL CONDITIONS	CATALYSTS		
	Cobalt with Cu/ZnO/Al ₂ O ₃	Ruhrchemie (precip. Fe)	C-73 (fused Fe)
Conversion	40.0	34.0	38.0
Feed H ₂ /CO	1.0	0.7	0.9
HYDROCARBON SELECTIVITY (wt. %)			
C ₁	8.5	6.2	9.8
Σ C ₂ -C ₄	14.6	24.6	38.5
Σ C ₅ -C ₁₂	52.6	41.2	43.4
Σ C ₁₃ -C ₁₉	18.5	18.9	7.7
Σ C ₂₀ -C ₃₀	5.8	8.4	0.6
ADDITIONAL SELECTIVITY			
Oxygenates (wt. %)	0.9	8.9	9.1
1-Butene/n-Butane (molar ratio)	0.37	3.54	4.08

Figure 1. Start-up conversion for cobalt combined with a Cu/ZnO/Al₂O₃ catalyst (Run 1). Flow=1 Nl/min; T=240°C; P=0.79 MPa; H₂/CO=1.

Figure 2. Stable usage ratio during start-up for cobalt combined with a Cu/ZnO/Al₂O₃ catalyst (Run 1). Flow=1 Nl/min; T=240°C; P=0.79 MPa; H₂/CO=1.

log C1-C12 normalized mol fraction

Figure 3. Typical light gas Schulz-Flory cobalt catalyst combined with a Cu/ZnO/Al₂O₃ catalyst (Run 1). Flow=1 Nl/min; T=240°C; P=0.79 MPa; H₂/CO=1.

Figure 4. Linearly regressed values of α_1 for the start-up of Run 1 of cobalt catalyst combined with a $\text{Cu/ZnO/Al}_2\text{O}_3$ catalyst. Flow=1 Nl/min; T=240°C; P=0.79 MPa; $\text{H}_2/\text{CO}=1$.

Figure 5. Effect of carbon number on the light gas selectivities to alkanes and alkenes. Flow=1 Nl/min; T=240°C; P=0.79 MPa; $H_2/CO=1$.

Figure 6. Time-on-stream dependence of C_4 selectivity. Flow=1 Nl/min; $T=240^{\circ}\text{C}$; $P=0.79\text{ MPa}$; $H_2/CO=1$.

Figure 7. The extent of water-gas-shift during the five material balances of Run 1 of cobalt combined with a $Cu/ZnO/Al_2O_3$ catalyst. Flow=1 Nl/min; T=240°C; P=0.79 MPa; $H_2/CO=1$.

Figure 8. Schulz-Flory diagrams of the five material balances of Run 1 of cobalt combined with a $\text{Cu/ZnO/Al}_2\text{O}_3$ catalyst. Flow=1 Nl/min; $T=240^\circ\text{C}$; $P=0.79\text{ MPa}$; $\text{H}_2/\text{CO}=1$.

Figure 9. Fit of C_3 - C_{18} data (material balance 4, 189 hours-on-stream) to regression developed by Donnelly et al. (1988). Note C_3 and C_4 lies well below line.

Figure 10. Semilogarithmic plot of mole fractions of various components (material balance 4, 189 hours-on-stream).

Log (Relative Mole Fraction)

Figure 11. Analysis of pot liquid. Linear regression value of $\alpha_2=0.86$. Note C_{32} , C_{44} , and C_{46} omitted due to impurities. C_{28} is liquid carrier.

Figure 12. Deactivation of Fischer-Tropsch activity of cobalt catalyst in combined catalyst system.

END

**DATE
FILMED**

3 / 16 / 93